

# Minerals yearbook 1942. Year 1942 1943

Pehrson, E. W.

Washington, D. C.: Bureau of Mines: United States Government Printing Office, 1943

https://digital.library.wisc.edu/1711.dl/PPYAWXJZXOESO8L

http://rightsstatements.org/vocab/NoC-US/1.0/

As a work of the United States government, this material is in the public domain.

For information on re-use see: http://digital.library.wisc.edu/1711.dl/Copyright

The libraries provide public access to a wide range of material, including online exhibits, digitized collections, archival finding aids, our catalog, online articles, and a growing range of materials in many media.

When possible, we provide rights information in catalog records, finding aids, and other metadata that accompanies collections or items. However, it is always the user's obligation to evaluate copyright and rights issues in light of their own use.

#### UNITED STATES DEPARTMENT OF THE INTERIOR

HAROLD L. ICKES, Secretary

**BUREAU OF MINES** 

R. R. SAYERS, Director


# MINERALS YEARBOOK 1942

Prepared under the direction of E. W. PEHRSON, Chief Economics and Statistics Service

C. E. NEEDHAM, Editor



UNITED STATES
GOVERNMENT PRINTING OFFICE
WASHINGTON: 1943



geologi MNK 610551 <u>HA</u> 1942

## **FOREWORD**

Minerals Yearbook, 1942, presents the achievements of the mineral industries of the United States during their first full year of World War II. It is a record of outstanding accomplishment to which the Nation can point with pride and satisfaction. It also provides convincing testimony on the vital importance of our great mineral wealth to the national security, for without our abundant mineral resources our unparalleled industrial strength would be impossible, and without our magnificent industrial machine the unprecedented production of munitions during 1942 could not have been attained. Thus in large measure our success in war on land or sea or in the air reflects our ability to provide those materials indispensable to modern warfare—

metals and fuels and the other nonmetallic minerals.

Statistically the production of minerals in 1942 soared to new peaks in both quantity and value. For the first time in history, the aggregate value of mineral output exceeded \$7,000,000,000. Certain branches of mining reported declines from the rates established in 1941, but production of many commodities reached new records, some of which probably will stand for many years or may never be equaled. Nevertheless, demand exceeded supplies, and the pressure for even greater output intensified as the year progressed. At the close of 1942, it was evident that production of many minerals would be limited by manpower shortages, while exhaustion of the reserves of a few commodities caused anxiety as to our ability to maintain current rates of production.

The Bureau of Mines played an increasingly vital role in the war program during 1942. Extensive exploration of mineral deposits was continued; new and improved methods of mineral beneficiation and recovery were developed; surveys of the production, distribution, consumption, and stocks of essential minerals were extended in scope and frequency; health and safety measures were furthered to reduce valuable time lost in the mines and mills from illness and injuries; provisions were made to protect the production, supply, storage, and transportation of indispensable minerals and mineral products from the mines, quarries, mills, and smelters; and closer contact was effected with Federal war agencies and private war industries in prosecuting the war. Most of these activities are only briefly mentioned in this volume, which is concerned principally with the ac-complishments of the Bureau in economics and statistics. More complete data regarding the Bureau's work in technology, health, and safety can be found in the annual reports of the Secretary of the Interior and in other publications of the Bureau of Mines, although censorship precludes publication at this time of many of the results of investigations of strategic and critical minerals.

Distribution of the 1942 edition of Minerals Yearbook, as with the 1941 volume, will be restricted to Government offices engaged in war work. Many of the chapters of the 1941 volume dealing with non-strategic commodities, minus complete data on foreign trade, were released for public distribution, but because of the refusal of the

THE SECTION AS

censorship authorities to permit publication of foreign trade statistics most of these chapters for 1942 will be withheld. Only a few chapters, from which foreign trade statistics have been eliminated, because they have little significance, will be available for general distribution. To partly offset this disadvantage, the Bureau of Mines has expanded its usual published Mineral Industry Survey reports to include many of the statistical details on production, consumption, and stocks of the nonstrategic minerals that are customarily distributed to industry and the public in the preprint chapters of Minerals Yearbook. Minerals Yearbook will, of course, be available to the public after the war

or whenever censorship restrictions are relaxed.

The mineral industries are to be commended for their cooperation in responding to Bureau of Mines surveys in spite of the numerous handicaps and urgent production schedules under which they operated in 1942. Thanks are gratefully extended to the thousands of mine, mill, and smelter operators, distributors, consumers, public officials and agencies, and trade journals who made generous contributions of data and advice, without which this volume could not be compiled. In this connection, especial mention should be made of the cooperation of State officials who have assisted in collecting mineral statistics within their respective jurisdictions, thus eliminating duplication and improving coverage and accuracy of data. State agents cooperating in the 1942 canvass were: Stewart J. Lloyd, acting State geologist, University, Ala.; Herman Gunter, State geologist, Tallahassee, Fla.; Garland Peyton, director, division of mines, mining, and geology, department of natural resources, Atlanta, Ga.; M. M. Leighton, chief, and Walter H. Voskuil, mineral economist, State geological survey division, Urbana, Ill.; A. C. Trowbridge, director, Iowa Geological Survey, Iowa City, Iowa; Raymond C. Moore, State geologist, Lawrence, Kans.; Edward B. Mathews, director, department of geology, mines, and water resources, board of natural resources, Baltimore, Md.; R. A. Smith, State geologist, Lansing, Mich.; H. A. Buehler, State geologist, Rolla, Mo.; Meredith E. Johnson, State geologist, Trenton, N. J.; C. A. Hartnagel, State geologist, New York State Museum, Albany, N. Y.; Jasper L. Stuckey, State geologist, Raleigh, N. C.; Robert H. Dott, director, Oklahoma Geological Survey, Norman, Okla.; E. P. Rothrock, State geologist, Vermillion, S. Dak.; E. H. Sellards, director, bureau of economic geology, Austin, Tex.; Arthur Bevan, State geologist, and Linwood H. Warwick, chief clerk, Virginia Geological Survey, Charlottesville, Va.; Harold E. Culver, supervisor, division of geology, department of conservation and development, Pullman, Wash.; Paul H. Price, State geologist, Morgantown, W. Va.; and E. F. Bean, State geologist, Madison, Wis. In addition, B. D. Stewart, department of mines, Juneau, Alaska, and Walter W. Bradley, In addition, B. D. State mineralogist, San Francisco, Calif., assisted in the compilation of statistics for Alaska and California, respectively.

R. R. SAYERS, Director.

## CONTENTS

oreword, by R. R. Sayersntroduction, by C. E. Needham
atroduction, by C. E. Needham
ort I (teneral summary:
Review of the mineral industries in 1942, by E. W. Pehrson
International aspects of war mineral procurement, by J. S. McGrath
Statistical summary of mineral production, by Martha B. Clark and
Marian E. Meyer
art II. Metals:
Aluminum and bauxite, by John H. Weitz and M. E. Trought
Antimony, by A. L. Ransome
Arsenic, by Allan F. MatthewsBauxite and aluminum, by John H. Weitz and M. E. Trought
Bismuth, by Allan F. Matthews.
Cadmium, by Allan F. Matthews
Chromite by Frederick Retz Jr
Cobalt, by H. W. Davis
Cobalt, by H. W. Davis  Copper, by T. H. Miller and H. M. Meyer  Ferro-alloys, steel, iron ore, and pig iron, by Norwood B. Melcher and
Ferro-alloys, steel, iron ore, and pig iron, by Norwood B. Melcher and
Edward J. Langey
Edward J. LangeyGold and silver, by C. E. Needham
Cold cileron connon load and ging in
Alaska, by Chas. W. Henderson  Arizona, by G. E. Woodward and Paul Luff
California, by Charles White Merrill and H. M. Gaylord
Central States, by A. J. Martin
Colomado by Chag W Handerson
Eastern States by A J Martin
Eastern States, by A. J. Martin Idaho, by G. E. Woodward and Paul Luff
Montana, by G. E. Woodward and Paul Luff
Montana, by G. E. Woodward and Paul Luff  Nevada, by Charles White Merrill and H. M. Gaylord
New Mexico, by Chas. W. Henderson
Oregon, by Charles White Merrill and H. M. Gaylord
South Dakota, by Chas. W. Henderson
Texas, by Chas. W. Henderson
Weshington by C. E. Woodward and Paul Luff
Washington, by G. E. Woodward and Taul Edit
Iron and steel scrap, by Harold E. Carmony and H. L. Cullen
Iron ore pig iron ferro-alloys and steel by Norwood B. Melcher and
Edward J. Langey  Lead, by T. H. Miller and A. L. Ransome  Lead and zinc pigments and zinc salts, by H. M. Meyer and A. W.
Lead, by T. H. Miller and A. L. Ransome
Lead and zinc pigments and zinc salts, by H. M. Meyer and A. W
Mitchell
Mitchell Magnesium, by John H. Weitz and M. E. Trought
Manganese and manganiferous ores, by Norwood B. Melcher Mercury, by H. M. Meyer and A. W. Mitchell
Mercury, by H. M. Meyer and A. W. Mitchell
Minor metals, by Allan F. Matthews
Molybdenum, by Frederick Betz, Jr., and Alice P. van Sicien
Nickel, by H. W. DavisPlatinum and allied metals, by H. W. Davis
Secondary metals—nonferrous, by F. H. Wright
Silver and gold, by C. E. Needham
Tin by C. E. Nighman and J. B. Umhau
Titanium, by Allan F. Matthews
Tungsten, by H. W. Davis.
Tungsten, by H. W. Davis
Zinc, by A. L. Ransome and J. H. Schaum  Zinc and lead pigments and zinc salts, by H. M. Meyer and A. W.
Zinc and lead pigments and zinc salts, by H. M. Meyer and A. W
Mitchell

#### CONTENTS

\
Part III. Nonmetals: Abrasive materials, by Robert W. Metcalf
Abrasive materials, by Robert W. Metcali
Asbestos, by Oliver Bowles and F. M. Barsigian
Asphalt and related bitumens, by A. H. Redfield
Barite, witherite, and barium chemicals, by Charles L. Harness and
K. G. Warner———————————————————————————————————
Carpon black, by G. R. Hopkins and H. Dackus
Cement, by Forrest T. Moyer and E. V. Balser
Clays, by G. W. Josephson and A. Linn
Coal:
Bituminous coal and lignitePennsylvania anthracite, by J. A. Corgan, J. W. Buch, and A. V.
remissivania anthracite, by J. A. Corgan, J. W. Buen, and A. V.
Coke and byproducts, by J. W. Buch, J. A. DeCarlo, and M. M.
Coke and byproducts, by J. W. Buch, J. A. Decano, and M. M.
Otero
Crude petroleum and petroleum products, by A. G. White, G. R. Hopkins, H. A. Breakey, and A. T. Coumbe
Coolition of Assertation I. W. Donie
Cryolite and fluorspar, by H. W. Davis
Feldspar, by Robert W. Metcalf
Fluorspar and cryolite, by H. W. Davis Fuel briquets and packaged fuel, by G. S. Goodman and G. E. Carlson
Com stones by Sydney H. Bell
Gem stones, by Sydney H. Ball Gravel and sand, by G. W. Josephson and G. E. Tucker
Cround spongtons tale and pyrophyllite by Portrand I Johnson
Ground soapstone, tale, and pyrophyllite, by Bertrand L. Johnson
and K. G. Warner Gypsum, by Forrest T. Moyer and M. G. Downey
Lime, by Forrest T. Moyer and F. D. Gradijan
Liquefied petroleum gases and natural gasoline, by G. R. Hopkins
and A. T. Coumbo
and A. T. Coumbe
Harness and Nan Jensen
Harness and Nan Jensen Mica, by G. Richards Gwinn and K. G. Warner
Minor nonmetals, by G. Richards Gwinn
Natural gas, by G. Ř. Hopkins and H. Backus Natural gasoline and liquefied petroleum gases, by G. R. Hopkins and
A T Coumba
A. T. Coumbe
Packaged fuel and fuel briguets by C. S. Goodman and G. F. Carlson
Post by Logonh A Cowoni
Peat, by Joseph A. Corgan Petroleum products and crude petroleum, by A. G. White, G. R.
Hopkins, H. A. Breakey, and A. T. Coumbe
Phosphate rock, by Bertrand L. Johnson and K. G. Warner
Potash, by Bertrand L. Johnson and K. G. Warner
Pyrites and sulfur, by G. W. Josephson and M. S. Jensen
Pyrophyllite, ground soapstone, and tale, by Bertrand L. Johnson and
K C Warner
K. G. Warner Salt, by F. E. Harris and K. G. Warner Sand and gravel, by G. W. Josephson and G. E. Tucker
Sand and graved by C. W. Locanbean and C. F. Tucker
Slate, by Oliver Bowles and M. S. Jensen
Stone by Oliver Bowles and M. S. Jensen
Stoné, by Oliver Bowles and M. S. Jensen Sulfur and pyrites, by G. W. Josephson and M. S. Jensen
Tale, pyrophyllite, and ground soapstone, by Bertrand L. Johnson
and K. G. Warner
Witherite, barium chemicals, and barite, by Charles L. Harness and
K. G. Warner
Out IV Mine selety:
Part IV. Mine safety: Employment and accidents in the mineral industries, by W. W.
Adams
Adamsndex_by_Mahel_E. Winslow

## INTRODUCTION

Considering the many difficulties of operation under wartime conditions, the mineral industries in 1942 established a remarkable record in supplying the essential needs of the United States for its military operations and civilian economy. This issue of Minerals Yearbook which records and analyzes the progress of the mineral industries during the year is therefore in essence a tribute to their achievements. The present expanded volume differs from its predecessors in a number of respects: It gives special attention to the significance of each of the many mineral commodities in the war program. It discusses the effects of the many emergency regulations of the Government upon the normal relationships of supply and demand. It provides more comprehensive data on ore reserves. It devotes additional space, in separate chapters, to titanium and nitrogen compounds. It accents the international aspects of mineral exploration, development, reserves, output, procurement, and use.

Because Minerals Yearbook, 1942, contains information on strategic and critical minerals, including full foreign trade data which censorship authorities have directed be withheld from the enemy, the volume has been classified as confidential. A few chapters dealing with nonstrategic commodities in which foreign trade is comparatively insignificant are being distributed to the public in preprint form without 1942 data on imports and exports. In the 1941 volume only 14 chapters were withheld from publication—those covering the highly strategic and critical items. The extension of censorship in the 1942 volume results largely from the ban on foreign trade figures. Statistical data for 1942 other than imports and exports for the non-strategic minerals have been released through the Bureau's Mineral

Industry Survey service.

Acknowledgments.—Thanks are gratefully extended to the Bituminous Coal Division, United States Department of the Interior, for its valuable contribution to the Yearbook in preparing the chapter covering the bituminous-coal industry. This division has supplied the chapter each year since the division was established in 1937.

The data on imports and exports in Minerals Yearbook were obtained through the cooperation of the United States Department of

Commerce.

The Bureau of Mines was enabled to obtain the vast amount of statistical data included in Minerals Yearbook through the good will and cooperation of those interested in the mineral industries. The Bureau appreciates more than ever the contributions of data from the operators, distributors, consumers, public officials, trade associations, and others who have so kindly given of their time and effort to return questionnaires or supply information in other form.

Credit for the value and usefulness of the volume is also given to the many members of the Bureau's staff who assisted in the preparation, editing, and arrangement of the Yearbook material. Especial thanks are due the following members of the staff, who have been most active and helpful in maintaining the high standards set for the Yearbook: Martha B. Clark, of the Economics and Statistics Service, for preparing the statistical summary of mineral production, and for ascertaining the accuracy, continuity, and uniformity of statistical data; Mabel E. Winslow, of the Office of Minerals Reports, for her excellent editorial work and advice; Louis F. Perry, of the Office of Minerals Reports, for his aid in preparing the charts; Max Abel, of the Economics and Statistics Service, for supervising the preparation of charts and assisting in the administrative details of the Yearbook program; and to the unnamed members of the Economics and Statistics Service who helped the authors in the preparation of their manuscripts.

C. E. NEEDHAM.

## PART I. GENERAL SUMMARY

## REVIEW OF THE MINERAL INDUSTRIES IN 1942

By E. W. Pehrson

#### SUMMARY OUTLINE

	Page		Page
Introduction	1	Government organization for war-Continued.	
Production	2	Office of Economic Stabilization	12
Trends in physical volume of production	2	War Production Board Office of Price Administration	12
Stocks	4	Board of Economic Warfare	15 16
Consumption	5	Petroleum Administration for War	17
PricesEmployment	6	Solid Fuels Administration for War	18
Safety	7	Bureau of Mines	
Government organization for war	10	Geological Survey Reconstruction Finance Corporation	20 20
Office for Emergency Management	îĭ	Government stock piles	20
Office of War Mobilization	. 11	Stimulation of domestic production.	21

#### INTRODUCTION

In the first year of World War II the mineral industry contributed metals, fuels, and other minerals—all indispensable for war—in quantities never before equaled. The physical volume of production was 3 percent more than in the previous record year 1941 and 21 percent higher than the predepression record of 1929; it exceeded the output in the war year 1918 by 54 percent. Owing to a moderate increase in mineral prices the value of production compared with 1941 was proportionately greater, having increased 10 percent to a new peak of \$7,569,500,000, or 8 percent above the former record value of \$6,981,340,000 established in 1920, when prices were abnormally high.

The outstanding performance for 1942 was achieved despite several factors that retarded production in some lines. Transportation bottlenecks forced severe curtailment of consumption of gasoline and fuel oil in the eastern region; as a result, the output of crude petroleum—in terms of value the largest item in the list of mineral products-Gold and silver production experienced the usual declined slightly. adverse effects of an ascending general price level and was also held back by scarcity of materials and manpower as well as the Government shut-down order effective late in the year. Price trends in 1942 did not favor the mineral industry, as mineral prices advanced only 7.5 percent over 1941, whereas the general price level rose 13 Manpower shortages were felt in many branches besides precious metal mining. Preliminary figures indicate that the total number of men employed in producing minerals in 1942 was 3 percent lower than in 1941. Because of the scarcity of critical materials and manpower, several new projects that would have increased production could not be initiated.

Consumption of minerals also reached new heights in 1942 that surpassed the available supply from domestic sources. Despite the submarine menace, large quantities of foreign minerals were imported but could not bridge the gap between domestic supply and potential demand. Consequently drastic conservation, substitution, and restrictive measures were adopted. Essential civilian requirements were cut deeply, and even allocations to war needs were subjected to rigid surveillance and limitation. The net result of the program was a gain in mineral inventories for the year. Thus at the end of 1942 the Nation's mineral-production facilities were operating at record rates, and a substantial reserve stock provided assurance that the essential war needs would not be severely impaired in 1943 for lack of raw materials.

#### PRODUCTION

Value of mineral output.—For the third consecutive year the quantity of minerals produced established a new all-time record, but the value of production exceeded the previous 1920 peak for the first time. Likewise, 1942 was the first year in which the value of domestic production, \$7,569,500,000, reached the 7-billion mark. The former record year, 1920, \$6,981,340,000, reflected the high prices of many minerals but chiefly the extraordinary prices for coal as exports soared because of the United Kingdom's inability (partly because of strikes) to meet heavy world demands. The value of the 1942 output was 10 percent greater than in 1941 and 29 percent over the predepression level of 1929.

Although dollar value is the only common denominator for measuring collectively the production of minerals of such diverse unit values as platinum and sand and gravel, it does not present a true picture of actual trends in the physical volume of production because of the influence of fluctuating prices. This fact is strikingly illustrated by comparing 1920 with 1942. The value of production in the latter year was only 8 percent above that of 1920, yet the physical volume of production, as measured by index numbers (in the computation of which the effects of price changes are largely eliminated), was 55 percent greater. Thus the growth of the mineral industry during this 22-year period and the industry's war contribution are not adequately revealed by a mere statement of value of output.

Of the total value of mineral production in 1942, fuels contributed \$4,084,600,000 (54 percent), metals \$2,361,800,000 (31 percent), and nonmetals other than fuels \$1,123,100,000 (15 percent). Figure 1 shows the growth in value of various branches of mineral production from 1880 to 1942.

All major branches of mineral production—fuels, metals, and nonmetals—showed increased values in 1942. The value of the output of metals advanced 11 percent over 1941 and that of nonmetals other than fuels 8 percent; the value of fuels rose 10 percent. Oil and gas wells contributed a large proportion of the mineral output, with products valued at \$2,452,700,000 in 1942—32 percent of the total and an increase of 5 percent over 1941. Hard- and soft-coal production was valued at \$1,631,900,000, or 22 percent of the value of all mineral products and 19 percent more than the value of the 1941 coal output.

Trends in physical volume of production.—Figure 2 compares the physical volume of mineral production during the last 43 years with industrial and agricultural production and with population growth, each

ことは、ことには、大人をなることとをあるといすが

expressed in terms of an index based on yearly averages for 1935–39.¹ The long-time trends of production during this 43-year period have been steadily upward, although year to year and cyclical fluctuations have been prominent. Production of minerals—the essential raw materials for industry—has been closely correlated with the trend of industrial production, experiencing the same ups and downs, whereas agricultural production has exhibited more moderate fluctuations and a growth line approximating the trend of population increase.

Because production of coal for domestic use and petroleum for automobile fuel, which has a pronounced effect on the trend of mineral output, does not respond proportionately to increases in the rate of




FIGURE 1.—Trends in value of mineral production in the United States, 1880-1942.

manufacturing activity and is more stable, the index of industrial production tends to exceed that of mineral production in periods of prosperity and to fall below during depressions. This characteristic explains in part the wide gaps between the two indexes in 1941 and 1942. Another factor is the extensive use of imported mineral raw materials in these years, which is reflected in the industrial index but not in the mineral index. It should also be noted that the Federal Reserve Board index of mineral production does not include certain mineral products, such as aluminum and magnesium, of which war use has increased greatly.

The production of many mineral commodities achieved new peaks in 1942. The light metals made outstanding advances; magne-

<sup>&</sup>lt;sup>1</sup>The following indexes have been used—volume of farm production, U. S. Department of Agriculture; mineral production, 1900-1918, from Warren Persons' Forecasting Business Cycles; mineral production of 1919-42 and industrial production, Federal Reserve Board; total population of the United States, Bureau of the Census.

sium output increased threefold, bauxite more than doubled, and aluminum rose nearly 70 percent. Copper production broke the record established in 1916, and lead and zinc mine production also increased but failed to reach previous records. Iron ore, tungsten, molybdenum, and vanadium surpassed the high production rates of 1941, and chromite exceeded its 1918 peak. Manganese-ore production was considerably higher in 1942 than in 1941 but was below that during the last war. Except for petroleum (which declined from 1941) and anthracite, the output of fuels reached new highs in 1941, and bituminous coal broke a record that had stood since 1918.

THE REPORT OF THE PERSON OF TH




FIGURE 2.—Comparison of growth of physical volume of mineral production with that of agricultural and industrial production and population, 1900–1942.

Most of the building materials also set new high marks, reflecting the heavy war construction in 1942. Production of fluorspar, lime, potash, pyrites, sulfur, and salt advanced to new heights. Contrary to this pronounced upward trend were the decreases noted in the output of gold, silver, petroleum, asphalt, feldspar, gypsum, and phosphate rock.

#### STOCKS

Inventory-control schemes were in effect, directly or indirectly, for virtually all metals and important nonmetals during 1942. Idle, excessive, and enemy-owned inventories were also called upon to help effectuate the maximum output of war equipment and bolster

a shrinking volume of essential civilian supplies. Conservation, substitution and reclamation, fluctuating imports, and rapidly changing Lend-Lease needs affected relative requirements and resulted in shifts of position in critical mineral lists. As a result, there was a wide range in stock trends for individual minerals during the year, but on the whole there was a general, and in some items, a substantial, increase in stocks.

The primary acquisition of many minerals, and other commodities as well, by government agencies was greatly extended during the These purchases can no longer be considered as stock-pile accretions but only as inflow to a reservoir from which the discharge is channeled to the most desirable destination. In some commodities industry stocks were drawn upon for current needs while Government holdings were expanded; manganese ore, chromite, muscovite mica blocks and films, tin, molybdenum, and cadmium were typical examples. There was a net increase in the Nation's total inventory of the first three items; but stocks of tin, cadmium, and molybdenum declined, the last substantially. Industry and Government stocks of copper, lead, zinc, tungsten ore, vanadium, mica splittings, mercury, antimony, platinum, and bauxite were larger at the end of 1942 than at the beginning. There were also increases in industry stocks of nickel, acid-grade fluorspar, iron ore, and magnesium, whereas stocks of metallurgical-grade fluorspar and cement were lower. Consumers' stocks of pig iron declined moderately, but there were fairly heavy increases in consumers' and suppliers' stocks of scrap iron and steel. There was little change in stocks of anthracite, bituminous coal again showed an increase, and stocks of petroleum showed an over-all decrease.

#### CONSUMPTION

Mineral consumption again broke all records in 1942 and was still on a rising trend at the year end. For virtually all metals and some nonmetals, unrestricted demand would have exceeded supply but was held in check only by widespread curtailment of civilian uses. Even the amounts of materials for use in war essentials were subject to rigid scrutiny and limitation, and the substitution of less critical for

more critical materials was actively pushed.

As the seriousness of the supply situation became apparent there was evolved a Production Requirements Plan (P. R. P.) in which the end use of the basic material was the governing factor in making allocations. It failed, however, to achieve the anticipated balance between supply and demand. Later in the year it was announced that the P. R. P. would be succeeded in 1943 by the Controlled Materials Plan (C. M. P.), which would be applied initially to aluminum, copper, and carbon and alloy steels. The new plan shifts control to the raw-materials source, thus requiring knowledge of material requirements throughout the manufacturing cycle down to the end product. By controlling allocations at the source, the balancing of allocations with available supply is facilitated. Responsibility for assembling estimates of raw-material requirements was placed with prime contractors, who are required to plan not only for their own needs but for those of their subcontractors and suppliers as well. Bills of materials so determined are then submitted to a

prime contractor's "claimant agency" of which seven were designated in the original order—Army, Navy, Maritime Commission, Board of Economic Warfare, etc. Each claimant agency assembles its bills of materials and submits them to the War Production Board, where they are balanced with available supply by a Requirements Committee and the respective controlled materials divisions of the War Production Board.

The year 1942 was characterized by a continuation of the war plant construction program, the near-conclusion of existing plant conversion and expansion, and a rapidly accelerated growth in war production. The thereby-expanded mineral needs are reflected by business indexes. The value of construction contracts awarded east of the Rocky Mountains (of which more than 80 percent were for public ownership) rose 37 percent from 1941 or to 8½ billion dollars in 1942. Of the year's total, only 22 percent was for residential building, including a part applied to war housing. Of the remainder, 35 percent was for factory construction and 40 percent for public works and utilities. The Federal Reserve Board index for total construction (1923-25 equals 100) fluctuated monthly between 118 and 206 and averaged 166 for the year. For other than residential building the index increased from 149 in 1941 to 235, another new record. The adjusted index of total industrial production (1935-39 equals 100) continued the rise that began in the latter half of 1940, increased uninterruptedly from 171 in January 1942 to 197 in December, and averaged 181 for the year (unadjusted) compared with 156 in 1941 and 123 in 1940.

Control of the second of the s

Consumption of minerals established many new highs in 1942. Among the metals, aluminum, chromite, copper, iron, magnesium, manganese ore, and other ferro-alloy elements reached new levels, but the use of tin, zinc, and lead declined under rigid control measures. Of the nonmetals, cement, lime, clay, fluorspar, sulfur, sand and gravel, phosphate rock, and potash exceeded previous records. In the fuel group, the demand for petroleum was held slightly under the 1941 peak by transportation difficulties; use of anthracite rose appreciably but still lagged behind the record, but bituminous-coal, natural-gas, and natural-gasoline consumption attained new peaks.

#### PRICES

A weighted average price for 24 major mineral commodities in 1942, which comprised over 98 percent of the total value of mineral production in that year, indicates an increase of 7.5 percent in producers' unit sales realizations compared with 1941. The average increase for the 9 metals in the group was 12.6 percent, that for the 5 fuels was 5.4 percent, and that for 10 other nonmetallic minerals was 5.3 percent. The relatively greater price rise for metals reflected premium prices paid by the Government for copper, lead, and zinc and the general pressure for increased metal production.

According to the Bureau of Labor Statistics, the wholesale price index (1926 equals 100) of metals and metal products rose from 99.4 in 1941 to 103.8 in 1942. The price index for nonferrous metals, which includes some fabricated products and excludes premium prices paid for copper, lead, and zinc, advanced from 84.4 to 85.7. Quoted prices for lead, zinc, antimony, cadmium, platinum, and mercury averaged higher in 1942 than in 1941; those of copper and

2.3

1. Co . Lat. 1. Co.

nickel were unchanged; and those of aluminum, magnesium, and tin declined, the last only slightly. The index for iron and steel products advanced less than 1 percent—from 96.4 to 97.2. Prices of ferrous raw materials, however, were virtually unchanged. Those for pig iron and most grades of scrap iron and steel were fixed throughout the year at ceiling prices; average pig iron and iron-ore prices for 1942 remained at 1941 levels, whereas the major scrap items were lower. Compared with 1941, fuel prices rose moderately. The price index for anthracite advanced from 82.7 to 85.5; bituminous coal from 104.3 to 109.7; and petroleum and its products from 57.0 to 59.8. Except for crushed stone and clay, which declined, building-material prices (brick and tile, cement, lime, and sand and gravel) increased, as did prices for phosphate rock and potash. The index price for all commodities rose 13 percent or from 87.3 in 1941 to 98.8 in 1942.

Mineral prices again lagged appreciably behind those for all commodities in 1942; the former increased only 7.5 percent over 1941, whereas the general price level rose 13 percent. Compared with 1929, the general price index in 1942 had increased 3.7 percent, whereas the index for fuels and lighting materials declined 5.4 percent (the index for petroleum and products dropped 16.1 percent), nonferrous metals 19.2 percent, and fertilizer materials 17.7 percent; the iron and steel price index rose 2.4 percent. Prices for nonmetallic minerals other than those included above averaged lower in 1942 than in 1929. In comparison with prices that prevailed in the First World War, when needs were far below those of the present, the price index for all commodities in 1942 was about a quarter below, whereas the indexes for important mineral groups, iron and steel, nonferrous metals, and petroleum and its products, were one-third to one-half under those of 1918.

#### **EMPLOYMENT**

In contrast to the serious unemployment in the mineral industries a decade ago, major segments experienced a severe shortage of labor in 1942, particularly as regards workers in nonferrous and ferro-alloy fields. The exceptional demand for most of those metals required an increase of the labor force to permit maximum use of existing capacity. Voluntary enlistments and the draft continued to make inroads among employees, but more serious was the migration to construction projects and war-production plants, which offered higher wages and less arduous work under conditions more favorable than in the mines. Turn-over increased extraordinarily, and despite widespread hiring the net number of employees continued to decline. This condition was aggravated by the enforced replacement of skilled workers with inexperienced and less competent men.<sup>2</sup>

In the mining of copper, which has been designated the most critical of all the war required minerals, a shortage of labor seriously threatened the attainment of production goals that in themselves scarcely met essential war needs. By that time, labor shortages had also developed in the Tri-State and western mixed-metal mines, which were attempting to increase their output of zinc, the demand for which exceeded domestic production capacity; likewise in the ferro-alloys industry the lack of manpower was causing grave apprehension, with

<sup>&</sup>lt;sup>2</sup> In recognition of the pressing need for education in safety and the rapid development of efficiency in various phases of underground work, the Anaconda Copper Mining Co. initiated a training-in-work program at its Butte (Mont.) mines late in 1942. This program, the first of its kind, was described in the June 1943 issue of the Mining Congress Journal, pp. 20-27.

the situation at the world's greatest molybdenum mine especially serious. The light-metal production facilities in the West, then well on their way to completion and making an additional large drain on the labor reservoir, also experienced difficulty in obtaining an adequate

labor force.

Some alleviation of the labor stringency was effected by Federal agencies. The War Manpower Commission (W. M. C.) issued a stabilization of employment order, effective September 7, 1942, in the 12 Rocky Mountain and Pacific Coast States. This order was designed to retard the outward flow of nonferrous mine workers (and those employed in the lumber industry as well) and to reduce turnover, but it did not provide for new labor supplies. Workers in these "critical" occupations were required to obtain certificates of separation from the United States Employment Service (U. S. E. S.) before seeking a job, and no employer was permitted to hire such a worker unless he furnished a certificate of separation. A liberal policy was pursued in granting these certificates, and it has been reported that only 30 percent were denied. The effectiveness of the stabilization order is said to have been sharply limited by nonobservance on the part of both workers and employers and by the lack of adequate enforcement procedure.

The second constitution of the constitution of the second constitution of t

On September 10 National Selective Service headquarters instructed State directors to extend occupational deferment to any registrant from employment in nonferrous metal production, regardless of skill, and if any registrant left such employment to reclassify him and withdraw his designation as a "necessary man." Under these instructions Selective Service drafts declined sharply. In October, as an aid to W. M. C.'s recruitment program, authorization was given to pay transportation of western qualified workers, their families, and household goods to nonferrous mining districts, the beneficiary being required to accept employment for not less than 90 days. Incomplete returns indicate that about 4,400 men, mostly soldiers, were thus moved. In November, as a result of efforts made by W. M. C., the construction of 2,600 housing units was authorized, and actual work started within a week after the needs of each locality were determined.

Of major importance was the action of the War Department, which furloughed approximately 4,300 soldiers. Distribution to establishments that had been approved by the U. S. E. S. was made in October and November, as follows: 2,900 to copper mines, 800 to lead and zinc mines, 250 to molybdenum mines, 90 to tungsten mines, and the remainder to miscellaneous mines. The Office of Services of Supply (now the Army Service Forces) also authorized its officers to release workers employed at arsenals or other projects for mine work.

release workers employed at arsenals or other projects for mine work. The Gold Mine Closing Order, L-208, issued by W. P. B. on October 8, 1942, displaced about 2,700 workers by the end of the year. Of these 2,100 registered with the U. S. E. S.; about 60 percent were referred to nonferrous mines and about 30 percent to other essential activities. Further incentive to employment was the War Labor Board award of October 16, increasing wages of copper, zinc, and lead workers in Utah and Idaho. The increases of 50 cents or \$1 a day were conditioned upon continuity at work and upon certain productive standards. They were made retroactive to May 15 in Idaho and July 1 in Utah.

The result of these measures and those of the mine, mill, and smelter operators was a gain of roughly 5 percent in the number of employees

in the Nation's copper mines for 1941, and of 2 percent in the Mississippi Valley lead and zinc mines. In these sections of the mineral industry, some mines already had gone to a 7-day work week in 1941. The practice was considerably extended in 1942, and despite the higher rate of absenteeism that persisted throughout the year the average number of hours of employment per man for the year in the areas

mentioned above rose 7 and 13 percent, respectively.

Labor shortages in the coal industry were met in part by increasing the number of operating days at the mines. A 6-day week was initiated in the soft-coal mines late in 1942 and in the anthracite mines early in 1943. Bituminous-coal mines made a 12-percent gain in production in 1942 over 1941, with a 2-percent decline in the number of workers. Pennsylvania anthracite mines increased their output by 7 percent, with a personnel 6 percent under that of 1941. An 8-percent increase in the production of coke (beehive and byproduct) was accomplished by a 5-percent increase in the number of employees at the ovens.

For the industry as a whole, an all-time record of mineral production was accomplished with 3 percent fewer employees, but the average number of hours per man rose 11 percent, and the output per manhour—measured in value—remained close to the 1941 level.

#### SAFETY

Accidents to persons employed in the mineral industries were more numerous in 1942 than in 1941, and there was a slight increase in both fatality and injury rates. However, in the light of the substantial rise in accident rates experienced by industry as a whole in 1942 the safety record of the mining industry may be considered favorable. According to present reports, 1,878 deaths and 97,232 nonfatal lost-time injuries were caused by accidents in 1942, compared with 1,622 deaths and 90,334 injuries in 1941. This increase in the absolute number of accidents in 1942 was not materially out of alinement with the increased man-hours of exposure to risk. The amount of exposure to occupational hazards is measured by the number of man-days or manhours during which the employees are at work. The weighted average of the operating time of the mineral industries during 1942, according to information available at present, was 259 days, a gain of 25 days per employee or 11 percent more than the average for 1941. in man-hours, the amount of exposure to risk in 1942 was 1,550,000,000 hours, an increase of 7.6 percent. Considering the number of manhours worked and the number of accidents, the record for 1942 shows a fatality rate of 1.20 and an injury rate of 62.72 per million man-hours of employment compared with 1.13 and 62.69, respectively, for 1941. Thus, the production record of 1942, though showing an increase in the number of accidents, was achieved without materially disturbing the number of accidents in relation to the number of man-hours worked in 1941.

Although higher accident-frequency rates were reported by some branches of the mineral industries—such as lead-zinc mines in the Mississippi Valley States, gold and silver mines, slate quarries, and smelters—lower, more favorable rates were reported for some other groups, such as copper mines, miscellaneous metal mines (a group that includes mines producing metals declared "strategic" in the conduct of the war), marble quarries, trap-rock quarries, and beehive-coke ovens.

A special study of accidents to men engaged in the production of petroleum was conducted for the second consecutive year, 1942, and it revealed an accident-frequency rate of 17.97 per million man-hours of employment. This rate compares favorably with that revealed by a similar study covering 1941, which was 20.21 per million man-hours.

#### GOVERNMENT ORGANIZATION FOR WAR

In previous editions of Minerals Yearbook, Government organization for war insofar as it related to the mineral industries has been summarized under the heading National Defense Activity. This

review carries the record forward to July 1, 1943.

The initial step toward industrial mobilization was taken on August 9, 1939, when the short-lived War Resources Board was In May 1940, a second step was taken with the creation of the Advisory Commission to the Council of National Defense to supervise and expedite the Nation's defense program. Eventually this commission disintegrated, and out of it emerged the Office of Production Management in January 1941 and the Office of Priec Administration and Civilian Supply in April. In August 1941 the latter became the Office of Price Administration, and its civiliansupply functions were transferred to the Office of Production Manage-In addition to these agencies and the permanent Government bureaus, the following temporary organizations were in existence at the beginning of 1942 (all of them had some responsibility with regard to the production, procurement, and distribution of mineral raw materials): Office for Emergency Management, Board of Economic Warfare, Office of Scientific Research and Development, Office of Petroleum Coordinator for National Defense, Office of Solid Fuels Coordinator for War, National War Labor Board, and several subsidiaries of the Reconstruction Finance Corporation. Other agencies with functions more indirectly related to the mineral industries included: Office of Lend-Lease Administration; Office of the Coordinator of Inter-American Affairs; Supply, Priorities, and Allocations Board; Office of Defense Transportation; Office of Censorship; and others of minor significance to the mineral industries. THE PARTY OF THE P

Reorganization and expansion of Government war administration for industry continued in 1942. In January, the War Production Board replaced the Office of Production Management and the Supply, Priorities, and Allocations Board, with Donald M. Nelson as Director replacing the dual directorship of William S. Knudsen and Sidney In the same month a Combined Raw Materials Board was set up by the United States and Great Britain, with broad responsibility for effecting the most efficient use of the raw material resources of the two nations and for collaboration with the other United Nations along similar lines. The Reconstruction Finance Corporation, with its war subsidiaries, was transferred from the Federal Loan Agency to the direction and supervision of the Secretary of Commerce in Febru-April witnessed the creation of a War Manpower Commission, with Paul V. McNutt as Chairman, to establish policies and plan for the most effective use of manpower, and the delegation of broad powers to the Board of Economic Warfare in formulating policy and in directing the procurement of foreign materials for war purposes; under this authority the Board took over full responsibility for foreign purchases (except financing and warehousing) from the Reconstruction Finance Corporation in January 1943. In June 1942 the Office of War Information was set up to coordinate and determine policy for Government controls on information, and Congress passed a law creating a Smaller War Plants Corporation within the War Production Board, to insure that small business concerns will be used most effi-

ciently and effectively in the war program.

By late summer it had become evident that more rigid control measures were required to achieve stability on the economic front. An act of October 2, 1942, passed by Congress, amended the Emergency Price Control Act of January 1942. The new act reaffirmed the existing authority of the Office of Price Administration and also authorized the President to stabilize prices, wages, and salaries affecting the cost of living. On October 3 the President delegated his powers under this statute to a Director of Economic Stabilization working through an Office of Economic Stabilization. Another outstanding development during the latter half of 1942 was the delegation of much broader powers to the Petroleum Coordinator for War and his designation as Petroleum Administrator for War.

During the first half of 1943 few changes occurred in the Government's war administration for industry. In April the Office of Solid Fuels Coordinator for War was succeeded by the Solid Fuels Administration for War. Of major significance was the establishment of an Office of War Mobilization to coordinate the Nation's war program on the industrial front, announced by the President late in May. The new agency was given full authority to determine policy and issue orders to accomplish the maximum use of the Nation's natural and industrial resources, effective use of manpower not in the armed forces, stabilization of the civilian economy, and adjustment of such economy to war needs and conditions.

Further information regarding the status and internal changes of the more important of the afore-mentioned agencies follows, and details of the action taken during 1942 are given in the commodity chapters of

this volume.

Office for Emergency Management.—This is essentially an administrative agency of the Executive Office designed to maintain liaison between the President and the national war agencies and to facilitate coordination of the activities of the latter. Although many war functions have been established within the Office for Emergency Management it is essentially a clearing agency and is only remotely

related to war activities in the mineral industries.

Office of War Mobilization.—The Office of War Mobilization was established within the Office for Emergency Management by Executive Order 9347 of May 27, 1943, to provide for more effective coordination of the Nation's mobilization for war. The same order also created an advisory committee composed of the Director of War Mobilization, James F. Byrnes, Chairman; the Secretaries of War and Navy; the Chairman of the Munitions Assignments Board; the Chairman of the War Production Board; and the Director of Economic Stabilization. Fred Searls is Adviser on Production to the Office of War Mobilization. The mineral industries will have little direct contact with the Office of War Mobilization but to the extent that this agency determines policies and develops programs for the maximum use of the Nation's natural and industrial resources and coordinates the activities of the action agencies, its decisions will affect mining considerably.

Office of Economic Stabilization.—This agency was created by Executive Order 9250 on October 3, 1942, to control the inflationary tendencies that had become quite acute at that time. Byrnes was appointed Director of Economic Stabilization and was succeeded by Fred M. Vinson late in May 1943, when Byrnes became Director of War Mobilization. The Director of Economic Stabilization was authorized to formulate and to develop a comprehensive national economic policy relating to the control of civilian purchasing power, prices, rents, wages, salaries, profits, rationing, subsidies, and related matters for the purpose of effecting greater stability on the economic and industrial fronts. To advise the Director of Economic Stabilization, an Economic Stabilization Board was established consisting of the Director of Economic Stabilization as Chairman; the Secretaries of Treasury, Agriculture, Commerce, and Labor; the Chairman, Board of Governors, Federal Reserve System; the Director, Bureau of the Budget; the Administrator, Office of Price Administration; the Chairman, National War Labor Board; and two repre-

sentatives each for labor, agriculture, and management.

War Production Board.—The War Production Board, established in January 1942 as a successor to the Office of Production Management, is the chief government agency concerned with industrial production for war, including war administration of metals and the nonmetallic minerals other than fuels. The organization of the Board, as of May 1942, was briefly described in Minerals Yearbook. 1941. but since that time many changes have been made. A major reorganization was announced by Chairman Donald M. Nelson on July 8, 1942, for the purpose of tying economic and military strategies more closely together and making more effective the Board's determination of policies and programs governing the flow of materials. Batt was named Vice Chairman to serve as general assistant and deputy to Nelson. All program-development work was brought together under James S. Knowlson, who was designated a Vice Chairman for Program Determination. Other major operating units of the reorganized board included a Deputy Chairman for Program Progress (Ernest H. Kanzler) and a Director General for Operations (Amory All industry and commodity divisions were transferred Houghton). to the Director General for Operations with A. I. Henderson, formerly chief of the old Materials Division, in immediate charge as a Deputy Director General. On September 15, Kanzler succeeded Houghton, resigned, as Director General for Operations.

In September 1942 two new vice chairmen were appointed. Charles E. Wilson was designated Chairman of a new Production Executive Committee as well as Vice Chairman of the War Production Board and was assigned responsibility for seeing that programs and schedules for the war program were met. He thus became top production authority in the War Production Board. Ferdinand Eberstadt replaced Knowlson as Vice Chairman on Program Determination, was given control of the Director General for Operations, and at the same time took over the chairmanship of the War Production Board Requirements Committee. This gave him full responsibility for developing proper programs and schedules and for making materials available to meet them. Knowlson was transferred to other duties, while a new War Production Board Program Coordination Division was established under Eberstadt, with Donald D. Davis as Director. A. I.

Henderson resigned as Deputy Director General for Operations on

October 31, and Knowlson resigned in January 1943.

The adoption of the Controlled Materials Plan early in November 1942 resulted in further reorganization of the War Production Board. The offices of Program Determination and Operations were consolidated under Eberstadt, with Kanzler continuing as Director General for Operations. A Program Bureau with Davis as Director and a Facilities Bureau, Fred Searls, Director, were established directly under Eberstadt. Under Kanzler four Deputy Directors General for staff, industry divisions, field operations, and distribution-were appointed. On November 18 J. A. Krug, Deputy Director General for Distribution, announced the establishment of a Controlled Materials Plan Division, with Harold Boeschenstein as Director; he also was named Chairman of a Controlled Materials Board. At this time the industry and commodity branches, all of which had been reporting to a Deputy Director General for Industry Operations, were regrouped. The Iron and Steel, Tungsten and Molybdenum, Manganese and Chromite, and Nickel Branches were consolidated in a new Steel Division, which, together with the Copper and Aluminum-Magnesium Divisions—the three divisions coming under the Controlled Materials Plan—were placed directly under the Director General for Operations although working closely with the Controlled Materials Plan Division. The Mining, Mica-Graphite, Tin-Lead, Zinc, and Miscellaneous Minerals Branches were grouped in a Minerals Bureau under Joseph M. Scribner, Director. The Chemicals, and Cork and Asbestos Branches were merged with other industry branches in a Commodities Bureau, and the Building Materials Branch was placed in a Construction and Utilities Bureau.

The next major reorganization of the War Production Board took place early in March 1943, following the resignation of Eberstadt and the designation of Wilson as Executive Vice Chairman, with authority over all phases of War Production Board programs and activities. Meanwhile several minor changes had occurred. On November 23 an Office of Production Research and Development was established, with Harvey N. Davis as Director and C. K. Leith as Chief of its Metals and Minerals Branch. The announcement early in February of plans to coordinate and correlate the mineral programs of the various Government agencies working in this field was of particular interest to the mining industry. At that time a Mineral Resources Coordinating Division was established, which was to be aided by a Mineral Resources Operating Committee and a Minerals and Metals Advisory Committee. Howard I. Young was named Director of the new division and Chairman of the two committees. He also succeeded Scribner as Director of the Mineral Bureau.

The March 1943 reorganization was announced as a "major War Production Board shake-up." Ralph J. Cordiner, formerly Director General for War Production Scheduling, was named a Vice Chairman and special assistant to Executive Vice Chairman Wilson. Krug became Vice Chairman in charge of Materials Distribution and Chairman of the Requirements Committee, Donald D. Davis was appointed Vice Chairman for Operations, and Curtis Calder, who had succeeded Kanzler as Director General for Operations in January, was named

executive assistant to Wilson.

In June 1943 two labor Vice Chairmen were named—one to handle

liaison with the War Manpower Commission and the other to have

authority over labor production.

As of July 1, 1943, the members of the War Production Board and the organization units and staff dealing with policy or administration affecting the mineral industries were briefly as follows:

Members

Chairman Secretary of War Secretary of the Navy Secretary of Commerce Secretary of Agriculture

Lieutenant General in Charge of War Department

Production

Administrator, Office of Price Administration Chairman, Board of Economic Warfare Special Assistant to the President Chairman, War Manpower Commission Director, Office of Defense Transportation Petroleum Administrator for War

Staff

Executive Office of the Chairman: Office of War Utilities, Director Power Division, Director Manufactured Gas Division, Director

Natural Gas Division, Director

**Executive Vice Chairman** 

Controller of Shipbuilding Steel Division, Director Deputy Director

Asst. Director for Raw Materials and Fa-

Plant Facilities Branch, Chief

Metallurgy and Conservation Branch, Chief

Raw Materials Branch, Chief Asst. Director for Production

Asst. Director for Program and Distribution Asst. Director and Chairman Production Directive Committee

Asst. Director for Manpower Copper Division, Director

Aluminum and Magnesium Division, Director Asst. Director for Ferro-Alloys

Ferro-Alloys Branch, Chief Program Vice Chairman

Program Bureau, Director

Stock-Piling and Transportation Division, Director

Production Controls Bureau, Director

Operations Vice Chairman

Deputy Vice Chairman for Industry Operations Deputy Vice Chairman for Field Operations

Conservation Division, Director Salvage Division, Director

Redistribution Division, Director

Mineral Resources Coordinating Division, Di-

Mineral Resources Operating Committee, Chairman

Representing Board of Economic Warfare

Representing Reconstruction Finance Corporation

Representing Bureau of Mines Representing War Production Board

Donald M. Nelson Henry L. Stimson Frank Knox Jesse H. Jones Claude R. Wickard William S. Knudsen

Prentiss M. Brown Henry A. Wallace Harry L. Hopkins Paul V. McNutt Joseph B. Eastman Harold L. Ickes

J. A. Krug B. J. Sickler Alexander Macomber Vacancy C. E. Wilson William Francis Gibbs John T. Whiting Norman W. Foy Carl W. Meyers

· 在一个时间,一个时间,一个时间,我们就是一个时间,我们就是一个时间,我们就是一个时间,我们就是一个时间,我们就是一个时间,也是一个一个一个一个一个一个一个一

Julius A. Claus H. J. French

W. C. Kerber J. V. Honeycutt J. L. Block C. H. Longfield

H. J. Ruttenberg Harry O. King A. H. Bunker Miles K. Smith Andrew Leith J. A. Krug John F. Fennelly W. Y. Elliott

Harold Boeschenstein Donald D. Davis John J. Hall Wade T. Childress Howard Coonley Paul C. Cabot Col. C. R. Baxter Howard I. Young

Howard I. Young

Alan Bateman

H. DeWitt Smith

Reginald S. Dean Harvey N. Davis

Theater

14.4

北京

Minerals and Metals Advisory Committee, Howard I. Young

Lt. Col. Joseph Woodlock, War Dept. Lt. Com. E. H. Augustus, Navy Dept. Alan Bateman, Board of Economic

Reginald S. Dean, Bureau of Mines H. DeWitt Smith, Reconstruction Finance Corporation.
Donnel F. Hewett, United States Geo-

logical Survey

Walter Janssen, Bureau of Foreign and Domestic Commerce

Stanley B. Adams, Office of Civilian Requirements, War Production Board

C. K. Leith, Office of Production Research and Development, War Production Board

Ellsworth R. Bennett, Facilities Bureau, War Production Board

Clinton Golden, Labor Production Division, War Production Board
W. Y. Elliott, Stockpiling and Transportation Branch, War Production
Board

Minerals Bureau, Director

Mica and Graphite Division, Deputy Director

Mining Division, Director Miscellaneous Minerals Division, Director

Tin and Lead Division, Director

Zinc Division, Director Commodities Bureau, Director Chemicals Division, Director

Cork, Asbestos, and Fibrous Glass Di-

vision, Director Consumers Goods Bureau, Director Construction and Utilities Bureau, Director Building Materials Division, Director Equipment Bureau, Director

Vice Chairman Procurement Policy Division, Acting Director Statistics Division, Director Office of Production Research and Development,

Office of Progress Reports, Director Office of Special Projects, Executive Officer Facilities Bureau, Director

Facilities Division, Director Vice Chairman for Civilian Requirements Metals and Minerals Division, Director Vice Chairman on Smaller War Plants

Vice Chairman (International Supply)

Howard I. Young M. H. Billings

Arthur S. Knoizen R. J. Lund

Erwin Vogelsang James Douglas H. D. Hughes D. P. Morgan Fred W. Gardner

Lewis S. Greenleaf, Jr. James Auten John L. Haynes Harry A. Rapelye

**Tudor Bowen** Stacy May Harvey N. Davis

Stacy May A. C. C. Hill, Jr. Charles E. Volkhardt William B. Murphy Arthur D. Whiteside S. B. Adams Brig. Gen. Robert W. Johnson William L. Batt

Office of Price Administration.—The Emergency Price Control Act of 1942, approved by the President on January 30, 1942, created the Office of Price Administration as an independent agency with statutory authority to enforce price-control measures. Before the passage of the act it had functioned only under general executive orders. The act was amended on October 2, 1942, to extend its period of effectiveness to June 30, 1944, and to convey broader powers to the President. As previously stated, these powers were delegated to the Office of

Economic Stabilization, which thus became the agency for determining

broad economic policy.

The general policy of paying subsidies for submarginal mineral production rather than stimulating output by general price increases has been continued. A General Maximum Price Regulation was issued on April 30, 1942, effective May 11, 1942, establishing maximum prices for all minerals for which ceilings previously had not been set (except "domestic ores and ore concentrates)" based on the highest price charged by seller during March 1942. The exemption of ores and concentrates had little significance because most of them were under contract to smelters under terms tied to metal prices, which were fixed, or were under contract to the Government at stipulated prices. Several revisions of the General Maximum Price Regulation were issued subsequently; details are given in the commodity chapters.

Prentiss M. Brown replaced Leon Henderson as Price Administrator in January 1943, and J. K. Galbraith resigned as Deputy Administrator of the Price Department in June 1943. As of July 1, 1943, the following units and executives of the Price Department were

administering prices for minerals:

Industrial Materials Price Division:

Director
Office of Metal Mining Analysis, Director
Building Materials Branch, Price Executive
Nonferrous Metals Branch, Price Executive
Iron and Steel Branch, Price Executive
Industrial Manufacturing Price Division, Director

Chemicals and Drugs Branch, Price Executive Fuel Price Division, Director Petroleum Branch, Price Executive Solid Fuels Branch, Price Executive Clair Wilcox
Jesse L. Maury
Neil Staebler
John D. Sumner
Donald D. Kennedy
Ben Lewis, Acting
Donald H. Wallace
Joseph D. Coppock
Sumner Pike
Orville Judd
G. G. Johnson

Board of Economic Warfare.—The most significant development in this agency in recent months, from the viewpoint of the mineral industries, was the transfer of authority and responsibility with respect to the procurement and production of imported commodities from the Reconstruction Finance Corporation to the Board of Economic Warfare. Under this arrangement, the Reconstruction Finance Corporation retained only accounting, financing, and warehousing functions in connection with purchases of foreign minerals. Further details of this transfer, as well as the Board's activities during the past year, are presented in the chapter International Aspects of War Mineral Procurement.

The foreign mineral procurement activities are largely centered in the Board's Office of Imports, under Morris Rosenthal. The technical staff of its Metals and Minerals Branch was as follows on July 1, 1943:

Acting Chief
Associate Chief
Chief Technical Consultant
Nonferrous Metals Division, Chief
Major Base Metals Section, Chief
Minor Base Metals Section, Chief
Ferro-Alloy Metals Division, Chief
Major Ferro-Alloys Section, Chief
Minor Ferro-Alloys Section, Chief
Scrap Metals Section, Chief
Industrial Minorals Division Acting Chief
Industrial Minorals Division Acting Chief

Industrial Minerals Division, Acting Chief Minor and Rare Metals Section, Chief Nonmetallic Minerals Section, Chief Paul H. Nitze Alan M. Bateman Chas. W. Wright Spencer S. Shannon Raymond Brooks Neil O'Donnell Vacancy Robert H. Ridgway Hugh E. McKinstry Benjamin Schwartz Kurt Lowenstein James S. Baker Vacancy

C. R. W. T. St. Co.

Technical Services Division, Chief
Analysis and Reports Section, Chief
Economics Section, Chief
Mine Service and Equipment Section, Chief
Foreign Plant Staff, Chief

Vacancy Robert K. Warner John W. Evans C. J. Pateneaux N. S. Maddock

Petroleum Administration for War.—On May 28, 1941, the President designated the Secretary of the Interior as Petroleum Coordinator for National Defense. The designation was changed on April 20, 1942, to the Office of Petroleum Coordinator for War, and by Executive Order 9276 of December 2, 1942, this agency became the Petroleum Administration for War with the Secretary of the Interior as Administrator ex officio, directly responsible to the President. The same order greatly extended the responsibilities and powers of the Administrator to establish basic policies and formulate plans and programs to assure for the prosecution of the war the conservation and most effective development and utilization of petroleum resources in the United States and to issue necessary policy and operating orders. Formerly the Coordinator was instructed only to "make specific recommendations to appropriate departments." The Petroleum Administration for War has also been designated as Claimant Agency for the petroleum industry under the Controlled Materials Plan.

As of July 1, 1943, the organization of the Petroleum Administration

for War was as follows:

Administrator—Harold L. Ickes
Deputy Administrator—Ralph H. K Davies
Assistant Deputy Administrator—R. E. Allen
Assistant Deputy Administrator—B. K. Brown
Assistant Deputy Administrator—E. L. DeGolyer
Chief Counsel—J. Howard Marshall
Executive Officer—E. L. Kohler
Director of Organizational Planning—L. S. Fish
Labor Counselor—F. H. Harbison
Production Division—Don R. Knowlton, Director
Refining Division—E. D. Cumming, Director
Transportation Division—J. R. Parten, Director
Marketing Division—Walter Hochuli
Natural Gas and Natural Gasoline Division—E. H.

Marketing Division—Walter Hochuli
Natural Gas and Natural Gasoline Division—E. Holley Poe, Director
Foreign Division—James Terry Duce, Director
Petroleum Reserves Division—W. B. Heroy, Director
Petroleum Supply Division—Vacancy
Materials Division—Frank A. Watts, Director
Facility Security Division—A. A. Jergins, Director
Research Division—Edward B. Swanson, Director
Public Relations Division—Gordon M. Sessions, Director
Program Division—Stewart P. Coleman

Cooperation and counsel from the industry are obtained through the Petroleum Industry War Council, headed by W. R. Boyd, Jr., District Industry Committees in each of five districts into which the country has been divided, and a Foreign Operations Committee. A National Conference of State Regulatory Authorities has been organized to coordinate the activities of the State regulatory bodies governing the production of crude petroleum and natural gas, with the programs of P. A. W.; and interdepartmental committees and boards provide for clearance of matters pertaining to the activities of the various agencies of the Federal Government concerned with petroleum. Field representation of the Petroleum Administration is accomplished through five district offices, with headquarters at New York, N. Y.; Chicago, Ill.; Houston, Tex.; Denver, Colo.; and Los

Angeles, Calif. The Petroleum Administration for War also has a representative in London and through the State Department main-

tains petroleum attachés in various other foreign countries.

Solid Fuels Administration for War.—This agency was established within the Department of the Interior by Executive Order 9332 on April 19, 1943, to centralize the Government's policies and to broaden its activities relating to solid fuels. It succeeded the Office of Solid Fuels Coordinator for War (so designated on May 25, 1942) which had been set up as the Office of Solid Fuels Coordination for National Defense at the request of the President to the Secretary of the Interior The Secretary of the Interior, serving ex on November 5, 1941. officio as Solid Fuels Administrator, is authorized to establish policies and formulate plans and programs to assure the most effective wartime conservation, development and utilization of solid fuels, to issue necessary policy and operating orders, and to appoint any necessary industry committees or councils. He is directed to compile data and make continuing surveys of the effect of prices on solid fuels and to recommend to the O. P. A. any needed maximum price adjustments; subject to the direction of the Chairman of the War Production Board, to provide adequate supplies of solid fuels for indirect military and essential industrial and civilian requirements and to effect proper distribution of critical materials allotted to the solid-fuels industries by the War Production Board; to determine the areas and times for the rationing of solid fuels; to recommend to the Office of Defense Transportation and to the War Shipping Administration action to provide adequate transportation of solid fuels; to request action by the War Manpower Commission on manpower requirements; and to obtain from private or Government sources information, statistics, and data required to effectuate his functions.

By Executive Order 9340, issued May 1, 1943, the Secretary of the Interior took possession and control of the Nation's larger coal mines in which stoppages or strikes had occurred or were threatened. Operation of these mines was handled by the Solid Fuels Administration through an organization set up for that purpose until the establishment of a coal-mines operating organization, to which that function was

transferred.

As of July 1, 1943, the organization of the Solid Fuels Administration was as follows:

Administrator—Harold L. Ickes

Deputy Administrator—Howard A. Gray
Associate Deputy Administrator—Thomas J. Thomas
Associate Deputy Administrator for Transportation—Fred A. Dawson
Assistant Deputy Administrator—Charles J. Potter
Assistant Deputy Administrator—Harlen M. Chapman

Assistant Deputy Administrator for New England—Oscar F. Ostby
Assistant Deputy Administrator at Seattle, Wash.—Vacant
Principal Assistant to the Associate Deputy Administrator—B. B. Brown
Technical Advisor—William F. Hahman

Head Conversion Engineer—Allen W. Thorson

Director, Information Division-L. W. Mosby

A Solid Fuels Advisory War Council, composed of representatives of mine producers, mine labor, coal transportation and distribution agencies, and the general public, provides cooperation and counsel. It is headed by Dr. Walter Dill Scott of Evanston, Ill., president emeritus of Northwestern University, a public representative.

Bureau of Mines.—Because of the importance of minerals in the

war program the Bureau's normal functions were quickly placed on a 100-percent war basis by a slight change in emphasis, accompanied by a substantial expansion in activity. While the Bureau had for years been conducting research on various phases of the strategic mineral problem, its present comprehensive war program was initiated following the passage of the Strategic Materials Act of 1939. At first investigations were largely restricted to the more critical materialsmanganese ore, chromite, tungsten, antimony, mercury, nickel, and As the defense program gained momentum this work was ex-Simultaneously industry's demands for raw materials began reaching unprecedented proportions, causing shortages in minerals of which the Nation had enjoyed self-sufficiency for decades. warfare and shipping shortages seriously threatened imports from certain Western Hemisphere sources which had previously been considered reasonably safe, even in war. As a result of these developments, the Bureau was obliged to extend its investigation of resources to include a great variety of raw materials; many of these required technical research to develop feasible methods of beneficiation.

Early in 1943 the Director of the Bureau of Mines reported that exploratory crews were at work in 48 States and Alaska and that since the start of the work in 1939 over 92,000,000 tons of war minerals (ore) had been charted, including 35,000,000 tons of the strategic minerals previously mentioned, 46,000,000 tons of iron ore, about 5,000,000 tons of bauxite in Arkansas, 3,000,000 tons of bauxite of various grades in other areas, 2,000,000 tons of alunite, and 1,500,000

tons of magnesium ores.

١

In addition to its extensive program of exploration, laboratory research, and pilot-plant testing, the Bureau's work in other fields was likewise oriented to war. Economic and statistical services were expanded to meet the demands of the war agencies for more and more data on production, consumption, stocks, and sources of minerals. Helium production was rapidly increased for use in blimps, balloons, and other military and civilian uses. The Bureau's petroleum experts were busily engaged in studying the numerous problems in petroleum supply and in seeking raw materials for aviation gasoline, synthetic rubber, and high explosives. Bureau engineers were called upon to help solve coal- and coke-supply problems that threatened to slow war production, and research on production of liquid fuels from coal was speeded in preparation for possible petroleum shortages, Promotion of health and safety continued unabated, not only for the protection of the workers in the mineral industry but to keep absenteeism through accidents at a minimum at a time when manpower was Other war jobs performed by the Bureau included administration of the Explosives Control Act and inspection of mines and plants with a view to recommending precautions against sabotage and other threats to production.

The operating structure of the Bureau was decentralized into three regional units during 1942 to facilitate field operations on war projects involving exploration and metallurgical testing, which were placed under the direction of three regional engineers and a corps of 23 district engineers. The Foreign Mineral Service established in 1935 was transferred to the Department of State and converted into a Mineral Attaché Service to advise on foreign mineral problems. The Bureau

of Mines will cooperate with the new service in a consulting and

supervisory capacity.

Geological Survey.—The Geological Survey staff was greatly enlarged during 1942, and its activities were almost completely diverted to war work. Its Geologic and Alaskan Branches, with the exception of the Military Geology Unit, which supplied vital information for the armed forces, were searching for war minerals in the United States, Alaska, and Latin America. Its Conservation Branch continued to administer mineral and fuel production from public lands and its expanded mapping and map-making facilities were hard-pressed to keep abreast of the enormous direct military demand for maps. The Water Resources Branch supplies data regarding water supplies for military and war-industry establishments, and several of its geologists were commissioned by the Army and assigned to solution of ground-water

problems in foreign territory.

In the minerals field, stress was laid on examinations of deposits and mining properties made at the specific request of various war agencies, and more than 700 reports were transmitted to them. Geologic studies of promising regions or districts with a view toward expediting company development or production directly or toward formulating recommendations for further exploration by the Bureau of Mines or the agents of the Metals Reserve Co. were carried forward as in the previous year. To provide closer cooperation with the Bureau of Mines after its decentralization, four regional offices were established in Spokane, Salt Lake City, Rolla, and College Park. These were staffed with geologists who could be assigned to Bureau of Mines projects so as to provide geologic guidance during actual exploration and to join in the estimation of reserves. Establishment of these regional offices made no change in the Survey's basic internal organization on a commodity basis wherein groups of geologists specialize on specific mineral commodities or geologically related groups of comInvestigation in Latin America in 1942 was carried on by field parties in Mexico, Cuba, Panama, Venezuela, Brazil, and Argentina. Reconstruction Finance Corporation.—Virtually all projects for increasing the supply of minerals for war are financed through this agency or its subsidiaries. In general, the Corporation acts on the requests of the War Production Board for domestic projects and the Board of Economic Warfare for foreign projects, but it maintains close scrutiny over all proposals. The activities of the Corporation and its subsidiaries are described in the chapter on International Aspects of

War Mineral Procurement.

#### GOVERNMENT STOCK PILES

Government purchases of minerals for stock-piling, price control, stimulation of production, preclusive buying, and other purposes continued at an accelerated rate in 1942. The wide variety of minerals and mineral products now being acquired by the Government and the extent to which the program has been expanded are indicated by the following list, which shows the items being purchased at various times:

As of end of 1941

Aluminum (refined) Antimony Asbestos Bauxite Beryllium ore Cadmium Chromium ore Cobalt Copper (refined)

Corundum ore Diamonds, industrial Graphite Iridium Iron ore Kyanite Lead (refined)

Lead ore

Lead vanadate concentrates Manganese ore Mercury Mica Nickel (refined) Nitrate of soda Platinum Quartz crystals Rutile Scrap iron Tin ore Tin Tungsten ore Zinc concentrates Zirconium ores

Added in 1942

Alumina Alumina (hydrate) Aluminum (reclaimed) Antimony ore Arsenic (crude) Arsenic (trioxide) Aviation gasoline Baddeleyite Beryllium oxide Bismuth Carbons (Brazilian) Cobalt-nickel compound Cobalt oxide Columbite Copper (matte)

Copper ore Corundum grain Cryolite ore Ferrochromium Ferromanganese Ferrovanadium Fluorspar Gold ore Iodine (crude) Iron (carbonyl) Lead (bullion)

Magnesite (deadburned) Magnesium Manganese-iron ore Molybdenite

Nickel (copper-refinery residues) Nickel (matte content)

Osminm Palladium Potash (muriate) Rhodium Ruthenium

Sapphire (natural Montana) Silver (foreign) Slags (tantalum-columbium)

Spodumene Strontium ores (celestite) Talc (steatite) Tantalite Tin (cast metal) Vanadium

Added in January-June 1943

Amblygonite Apatite (calcium phosphates) Arsenical speiss

Bismuth ore Coal Coke (petroleum) Diamond bort Diamond bort
Emery ore (Turkish)
Iron (pig)
Manganese (electrolytic)
Mica (amber phlogopite splittings)
Mica (amber phlogopite block)

Mica films Monazite sand Nickel (matte content) Nitrate (synthetic) Osmiridium Platinum ore Tin (reclaimed) Tin slags

Topaz

Many of the commodities shown are not obtained for stock-piling purposes but are purchased by the Government to centralize buying. particularly of foreign materials, to coordinate shipping, and to facilitate distribution of materials to the most essential uses. To effect the distribution of materials the War Production Board promulgated Imports Order M-63 late in December 1941; this prohibits any person, except Government agencies or their authorized representatives, from making arrangements for importing into the United States materials listed in the order, except under contracts existing at the effective date of the order or by special authorization from the The lists were revised several times during War Production Board. 1942 and at the end of the year included most of the mineral commodities being acquired by the Government.

The chief procurement agent for mineral raw materials is the Metals Reserve Co., although Defense Supplies Corporation also is an important participant in the program. Final responsibility for foreign purchases has been vested in the Board of Economic Warfare since April 1942. Details of the public purchases and stock-piling activity during 1942 are given in subsequent chapters of this volume.

#### STIMULATION OF DOMESTIC PRODUCTION

Several measures were adopted in 1942 to stimulate domestic production of critical minerals, all with a view to avoiding the extraordinarily high prices that prevailed during World War I, or to restrict payment of high prices to submarginal producers. A premium-price plan for copper, lead, and zinc was announced jointly by the Office of Price Administration and the Office of Production Management (now War Production Board) in January 1942. Under the plan substantial premiums were paid over established ceiling prices for production in excess of quotas determined by a joint committee of the Office of Price Administration and the War Production Board and approved by the Metals Reserve Co. Some of the original premiums announced in January were raised in December 1942 and again in February 1943, and many quotas were revised to offset rising costs of production and to bring in additional output where possible. During 1942 premiums paid by the Government in excess of ceiling

prices totaled approximately \$22,500,000.

As early as 1940 the Metals Reserve Co. began contracting for large quantities of domestic ores, particularly manganese ores, guaranteeing a market for fixed tonnages at stipulated prices. program was designed to get submarginal deposits of strategic minerals into production. However, it developed that some more flexible procedure was required to encourage small producers, so in March 1942 the company set up several buying depots where small tonnages of critical minerals would be purchased under price schedules issued from time to time. The original program has been expanded, and as of July 1943 about 30 purchase depots were operating in Arizona, Arkansas, California, Colorado, Montana, Nevada, New Hampshire, New Mexico, New York, North Carolina, Oregon, Utah, and South Dakota. Commodities purchased at these depots included chromite, manganese ores, mercury, tungsten ores, tin ores, antimony ores, vanadium ores, oxidized lead-zinc ores, beryl, molybdenum ores, mica, and columbite-tantalite ores. No one depot purchases all of these minerals, and some purchase only one or two.

Government-owned expansion of plant capacity for war mineral production is handled chiefly through the Defense Plant Corporation, which operates largely on recommendations from other war agencies charged with responsibility for administering the war program. The plants and equipment are owned by Defense Plant Corporation and operated by private industry under lease, management contract, or other arrangement. The Corporation receives rentals from the plants and in some instances has contracts for reimbursement by the war agency sponsoring the project. In the mineral field, the chief domestic commitments of this agency have been in petroleum pipe lines and in production facilities for aluminum, magnesium, steel, aviation


gasoline, tin, copper, chromite, manganese ore, and zinc.

In addition to the extensive activities of its subsidiaries—Metals Reserve Co. and Defense Plant Corporation—the Reconstruction Finance Corporation has stimulated mineral production by direct loans to industry. Mining loans were liberalized considerably during 1942. In March the Corporation announced that development loans on properties that give reasonable promise of success could be obtained without mortgaging the property and could be repaid out of proceeds from production. Public Law 603, approved June 11, 1943, authorized the Corporation to make loans up to \$5,000 to any one borrower for the purpose of financing the renovating, retimbering, or other preliminary development of mine workings, when such loans are deemed by the R. F. C. to be advantageous to the war program.

Prospecting and exploration assistance was given throughout the year by the Bureau of Mines and Geological Survey of the United

States Department of the Interior. Both agencies have expanded their staffs to increase war mineral production and to the extent permitted by available appropriations undertake geological investigations and exploration of ore deposits that might contribute to the war supply of minerals. In addition, the Bureau of Mines assists in determining improved methods for treating ores and in recommending to the War Production Board projects for increasing production.

Federal Aids for War Mineral Production, a pamphlet describing the various Government services for stimulating output, was issued by the War Production Board on December 15, 1942 (second edition).



### INTERNATIONAL ASPECTS OF WAR MINERAL PROCUREMENT

By J. S. McGrath

#### SUMMARY OUTLINE

	Page	kan jihan disabili kata di Kabupatèn P	age
ntroduction	25	Federal agencies engaged in foreign mineral	
Federal agencies engaged in foreign mineral		investigations—Continued.	
investigations	26	U. S. Commercial Co	28
Metals Reserve Co	26	Defense Supplies Corporation	29
Antimony	26	Russia	29
Chromite	26	Defense Plant Corporation	29
Copper Cryolite	27	Transfer of authority and responsibility	A
Cryolite	27	from Reconstruction Finance Corporation	
Industrial diamonds		to Board of Economic Warfare	30
Graphite	27	Board of Economic Warfare	30
Iron ore	27	Office of Exports	31
Lead	27	Office of Imports	31
Manganese Mercury	27	United States Department of State	31
Mercury	27	United States Department of the Interior	32 32
Mica	21	Geological Survey	32 32
Nickel	27	Bureau of Mines	33
Platinum	27 27	Other Federal agencies War Production Board	33
Quartz crystals Silver	27	Office of Coordinator of Inter-American	99
Tin	28		33
T111	28	Affairs	34
Tungsten Vanadium	28	MiscellaneousObjectives of research	34
Zinc	28	Objectives of research	33
Canadian agreement	28		
Canadian agreement	- 20		

#### INTRODUCTION

Entry into the war in December 1941 soon terminated the period of uncertainty as to the extent of this country's actual dependence on foreign sources for certain minerals. For a number of years there had been some agitation in official circles for the accumulation of mineral stock piles, but the Government took no precautionary action to anticipate inevitable shortages of many raw materials normally This period ended with the enactment by Congress of the Strategic Materials Act, Public 117, 76th Congress, 1st Session, approved June 7, 1939. The purchase from abroad or from domestic sources (if available) of strategic and critical materials, as defined by the Army-Navy Munitions Board, was authorized, and \$100,000,000 was to represent the total expenditure for stock piles under this act. The Procurement Division, Treasury Department, was designated as the Federal agency to purchase and stock pile the commodities specified by the Army-Navy Munitions Board. Limitations and definite restrictions in the original act retarded actual acquisition of the stock piles during the first year of operation under Public 117. The program received needed impetus in 1940 by enactment of Public 664, 76th Congress, 3d Session, approved June 25, 1940, which amended section 5 (d) of the Reconstruction Finance Corporation Act. Public 664 overshadowed Public 117 in importance. authorized the Reconstruction Finance Corporation to organize and finance corporations "to produce, acquire, and carry strategic and critical materials as described by the President." These broad

powers of Public 664 were extended by an amendment (Public 108, 77th Cong., 1st Sess.) approved June 10, 1941. Public 108 authorized the Reconstruction Finance Corporation "to take such other action as the President and the Federal Loan Administrator may deem necessary to expedite the National Defense Program." Thus the Reconstruction Finance Corporation was provided with effective legal authority for the Government purchasing program that was in operation throughout 1942.

Under authority of Public 664, approved June 25, 1940, the Reconstruction Finance Corporation created the Metals Reserve Co., the U. S. Commercial Co., the Defense Supplies Corporation, and the Defense Plant Corporation. All of these agencies are owned, managed, and operated under supervision of the Reconstruction Finance Corporation and all have played vital roles in the acquisition of strategic and critical materials required in the conduct of the war by this country and the other United Nations.

## FEDERAL AGENCIES ENGAGED IN FOREIGN MINERAL INVESTIGATIONS

#### METALS RESERVE COMPANY

This agency was created June 28, 1940, by the Reconstruction Finance Corporation and commenced operations with the object of building stock piles of strategic and critical metals and minerals. The program was expanded soon thereafter to include the sale of such materials when necessary in the defense program. At first, the company contracted for the purchase of materials upon a delivered basis, buying all such materials as would comply with requirements necessary to produce the required finished product. Later this program was expanded by the execution of agreements with the governments of foreign countries, particularly in South America, whereby all the exportable surplus of such countries was to be sold to the Metals Reserve Co.

Between the date of its creation on June 28, 1940, and October 31, 1942, Metals Reserve Co. made commitments aggregating \$3,224,-348,323, of which \$1,812,087,030 was for domestic activities and \$1,412,261,293 for foreign transactions. Of the total commitments, \$143,181,997 has been canceled, and some of the balance probably will not be used.

Antimony.—The company has contracted to purchase antimony produced in China, Mexico, Central America, and South America (chiefly Bolivia) at an approximate cost of \$12,698,000. Disbursements for deliveries totaled \$3,415,000 at the date of the latest company report.<sup>2</sup>

Chromite.—In purchasing chromite, principally for use by the steel industry in alloys, the company has contracted for production from seven countries outside the Western Hemisphere. Contracts for such production total approximately \$37,665,970. In addition, contracts have been made for chromite produced in Brazil, Cuba, Alaska, and

<sup>1</sup> See U. S. Tariff Commission, Latin America as a Source of Strategic and Other Essential Materials, Report 144.

<sup>&</sup>lt;sup>2</sup> For a complete report of this agency and other subsidiaries of the Reconstruction Finance Corporation see Report of the Reconstruction Finance Corporation, and Its Subsidiaries in Connection With the War, as of October 31, 1942.

TO THE SECOND STREET SECOND STREET SECOND STREET SECOND STREET SECOND STREET SECOND STREET SECOND SE

the United States at an approximate cost of \$26,774,295. Disburse-

ments for delivery total \$11,980,000.

Copper.—The company has contracted to purchase copper and copper ore, both domestic and foreign. Most of the copper and copper ore comes from other countries of the Western Hemisphere. Of the total cost of these purchases—\$328,428,926—\$226,203,716 has been disbursed in payment against deliveries. The copper is sold almost as rapidly as received. Defense Plant Corporation is also financing the expansion of two plants in the United States, in addition to those in Chile.

Cryolite.—The company has contracted for the purchase and im-

portation of cryolite ore at an approximate cost of \$5,308,000.

Industrial diamonds.—The company has purchased industrial diamonds from Brazil at a cost of \$5,765,000. Of this amount, \$4,250,000 has been disbursed for deliveries. The company has also contracted for crushing bort from other foreign countries at a cost of \$2,275,000.

Graphite.—Contracts have been made for graphite from foreign countries at a cost of \$5,480,000 (of which \$683,000 has been disbursed), as well as for the purchase of graphite of domestic origin.

Iron ore.—The company has contracted for the purchase of domes-

tic and Brazilian iron ore at an approximate cost of \$21,896,000.

Lead.—Contracts have been made for importing refined lead from four foreign countries and ore and concentrates from seven countries at a cost of \$107,497,000. Of this amount, \$47,511,000 has been disbursed for deliveries.

Manganese.—Contracts have been made for imports of manganese ore from 10 foreign countries as well as for domestic ore. The amount of all contracts will aggregate approximately \$149,453,000, of which \$33,058,000 has been disbursed for deliveries.

Mercury.—Mercury is being purchased from Mexico, Canada, and South American countries, as well as from domestic sources. Commitments total \$12,872,000, of which \$7,521,000 has been disbursed.

Mica.—Mica is being purchased from four foreign countries. Purchases aggregate \$9,673,000, of which \$1,861,000 has been disbursed

against deliveries.

Nickel.—In addition to the nickel to be produced by the facilities in Cuba financed by Defense Plant Corporation, Metals Reserve Co. has contracted for nickel and nickel-cobalt speiss for import at a cost of \$8,317,000. Of this amount, \$4,124,000 has been disbursed against deliveries.

Platinum.—The company has made commitments to purchase imported crude platinum at a total cost of \$1,707,000. Crude platinum contains platinum, iridium, osmium, ruthenium, palladium, and gold. The company has also purchased, at a cost of \$128,000, iridium produced in Russia and requisitioned by the War Department when delivered in New York.

Quartz crystals.—The company has contracted to import quartz crystals from Brazil at a cost of \$7,640,000. A total of \$6,929,000 has been disbursed for deliveries. Quartz crystals are necessary in radio manufacture.

Silver.—At the request of the War Production Board, and with the consent of the Secretary of the Treasury, it has been agreed to buy 10,000,000 ounces of foreign silver at 45 cents an ounce and make it available to industry under allocation by the War Production Board.

Tin.—Agreements with the International Tin Committee, starting June 28, 1940, provided for the purchase of 112,500 tons of refined tin produced in the Far East before December 31, 1941, for stock-pile purposes. In addition, the company agreed to purchase a minimum of 37,500 tons during the first 6 months of 1942, provided the International Scheme for the Regulation of Production and Export was renewed for a further term beyond December 31, 1941; the scheme, however, was not renewed. 41,596 tons of fine tin were received under this agreement, and 12,728 tons of fine tin were received in the form of tin ore for smelting in the Texas tin smelter—a total of 54,324 tons before the supply was cut off through enemy action. 11,700 tons of fine tin have been received from China and Belgian Congo. Tin ores have been received from Bolivia sufficient to manufacture 35,000 tons of fine tin, making a total already received of slightly more than 100,000 tons. A small amount has been sold.

Defense Plant Corporation constructed the Texas tin smelter at an approximate cost of \$6,300,000. This smelter will produce tin both from Bolivian ores and from Far Eastern alluvial ores. When the tin smelter started operations April 5, 1942, there were in stock pile Bolivian tin ores and Netherlands East Indies ores totaling approximately a year's capacity for the smelter, which is operated for account

THE REPORT OF THE PARTY OF THE

of Metals Reserve Co.

Tungsten.—The company has contracted to purchase tungstencontaining ores from eight foreign countries and from domestic producers. Commitments for the domestic and imported ores aggregate

\$166,112,000, of which \$19,220,000 has been disbursed.

Vanadium.—As practically all available vanadium from foreign and domestic sources is being purchased by American industry, the company has agreed to finance experimental test work for extracting vanadium from coal, crude oils, and iron ores in countries of the Western Hemisphere.

Zinc.—The company has contracted to purchase zinc and zinc ore produced in the United States and imported from eight foreign countries, at a cost of \$57,748,000. Of this amount, \$12,723,000 has been

disbursed for deliveries.

Canadian agreement.—On June 29, 1942, the company executed an agreement with War Supplies, Ltd., a Canadian company; under its terms the company will advance (from time to time) funds not exceeding \$10,000,000 to be used by the Canadian company for developing new sources of supply of copper, zinc, lead, and other strategic and critical materials and minerals required for the war effort. Under the terms of this agreement, all minerals produced from new projects developed by means of the funds advanced and also any increased production from existing projects resulting from expenditures made from such funds will be purchased by Metals Reserve Co. at cost of production and delivery. When such purchases are made, the advances for development will be amortized in the cost of the materials.

#### UNITED STATES COMMERCIAL COMPANY

This agency was created March 27, 1942. Its principal purpose is to compete in neutral countries, such as Spain, Turkey, and Argentina, with enemy powers for the purchase of any material that might be of use to the Axis Nations.

The company has established a working agreement with its British counterpart, the United Kingdom Commercial Corporation. The

The second of th

effect of this arrangement is to enable the U.S. Commercial Co. to utilize the facilities of the British company wherever they exist. The U.S. Commercial Co. also has representatives in a number of foreign countries.

This company will sustain proportionately heavy losses.

#### DEFENSE SUPPLIES CORPORATION

All procurement activities involving minerals that the war requires to be financed by the Reconstruction Finance Corporation, other than those handled by Metals Reserve Co., Defense Plant Corporation, and U. S. Commercial Co., are handled by Defense Supplies Corporation. Effective July 2, 1942, the Government assumed control over virtually all imported materials by amendment to War Production Board General Preference Order M-63.

Since its creation August 29, 1940, the corporation has made commitments aggregating \$3,650,725,563, of which \$2,511,303,120 is for domestic and \$1,139,422,443 for foreign activities. Of the total, \$334,347,105 has been canceled, and much more probably will not be used. Many of these activities will involve very substantial losses. These amounts involve mineral and all other commodities

and activities.

Commitments by Defense Supplies Corporation include \$1,499,-906,141 for the purchase of aviation gasoline and component parts and aviation-gasoline-plant expansion, essentially a domestic expenditure, and \$100,000,000 to Russia for metals and other materials.

Russia.—Before lend-lease aid was extended to Russia, Defense Supplies Corporation contracted with Amtorg Trading Corporation, a United States corporation owned by Russia, to purchase needed materials from the Soviet Union to the extent of \$100,000,000 and made an advance payment of \$49,668,248, in the form of a loan, against delivery, subject to the condition that such advance payment be used to purchase in this country supplies needed by the Soviet Union. Materials already shipped by the Soviet Union, through Amtorg Trading Corporation, including cargoes delivered or that have been sunk, include the following mineral commodities: Asbestos, chrome ore, dead-burned magnesite, potash, and platinum.

### DEFENSE PLANT CORPORATION

This agency has financed and contracted to finance the construction, equipment, partial equipment, or expansion of 1,337 plants for building or fabricating ships, bombing, fighting, transport, and cargo planes, tanks, heavy guns, ordnance, magnesium, aluminum, steel, tin, copper and other metals, synthetic rubber, high-octane aviation gasoline, machine tools, flying schools, pipe lines, etc., at an aggregate estimated cost of \$8,333,839,503; by November 1942 \$2,407,294,064 had been disbursed and \$798,239,768 canceled. Most of this construction activity has been within the United States, but the Defense Plant Corporation is financing facilities for producing additional copper in Chile at an estimated cost of \$4,999,850 and has agreed to finance another plant at an estimated cost of \$15,000,000. It is also establishing facilities, at an estimated cost of \$19,300,000, for producing nickel in Cuba and has authorized \$4,000,000 for constructing facilities for producing vanadium in Peru.

# TRANSFER OF AUTHORITY AND RESPONSIBILITY FROM RECONSTRUCTION FINANCE CORPORATION TO BOARD OF ECONOMIC WARFARE

Effective February 25, 1943, by order <sup>3</sup> of the Chairman, Board of Economic Warfare, the authority and functions of the four subsidiary companies of the Reconstruction Finance Corporation herein described as they pertained to imported materials, with the exception of their responsibilities relating to "the corporate execution of imported materials contracts, the disbursement of funds thereunder, the necessary accounting with respect to such disbursements, and the acceptance of delivery of commodities and materials," were transferred to the Office of Imports, Board of Economic Warfare.

### BOARD OF ECONOMIC WARFARE

The genesis of the Board as it now functions may be traced to Executive Order 8839 of July 30, 1941, which established the Economic Defense Board "for the purpose of developing and coordinating policies, plans, and programs designed to protect and strengthen the international economic relations of the United States in the interest of international defense." In order to define further the functions and duties of the Economic Defense Board with respect to the unlimited national emergency as declared by the President on May 27, 1941, the following Executive orders were promulgated:

No. 8900 of September 15, 1941, transferred the duties of the Administrator of Export Control and thus amended and extended the

powers of the original Executive order creating the Board.

No. 8926 of October 28, 1941, established the Lend-Lease Administration.

No. 8942 of November 19, 1941, provided for administration of the requisitioning of property required for national defense.

No. 8982 of December 17, 1941, changed the name of the Board as

originally created in July 1941.

No. 9128 of April 13, 1942, defined additional duties and functions

of the Economic Defense Board.

Amendment to Executive Order 9128, issued by the President on May 20, 1942, clarified and interpreted Executive Order 9128 in respect to certain functions of the United States Department of State and to relations with the Board of Economic Warfare.

Order 5, effective February 25, 1943, issued by the Vice President of the United States in his capacity of Chairman, Board of Economic Warfare, provided for additional delegations of authority to the Board and prescribed procedures and methods with respect to the procurement and production of imported commodities financed through the subsidiary companies of the Reconstruction Finance Corporation.

Attention is directed to the full texts <sup>4</sup> of Executive Orders 8839 of July 30, 1941; 9128 of April 13, 1942; the statement issued by the President on May 29, 1942, clarifying the relationship between the Department of State and the Board of Economic Warfare; and Order 5, effective February 25, 1943, issued by the Chairman, Board

of Economic Warfare.

<sup>&</sup>lt;sup>3</sup> Board of Economic Warfare, Order 5: Federal Register, vol. 8, No. 13, January 20, 1943, pp. 908-909.

<sup>4</sup> The text of all Presidential proclamations and Executive orders, and of rules and regulations issued by Federal agencies that have general applicability and legal effect appear in the Federal Register, published daily by the Division of the Federal Register, The National Archives, Washington, D. C.

As a war agency the Board of Economic Warfare has been vested with broad powers and responsibilities incident to the export from this country of all commodities to foreign neutrals and allied belligerents as well as to the importation of essential raw materials from such sources. One of the principal subdivisions of the Board has as its main objectives the control and direction of commodity export movements in such a manner that the power to supply essential materials can be used as a positive economic weapon in successful prosecution of the war.

Office of Exports.—In addition to other responsibilities and with special reference to mining and related activities, the Office of Exports directs the Board's action in such a way as: To expedite the flow of raw materials required by friendly countries for the war effort either in military or civilian operations; to prevent the export of raw materials consigned to unfriendly nations or individuals; to prevent excessive depletion of stocks of essential materials in this country; and to aid in supplying machinery and other necessary equipment for development and industrial projects in friendly foreign countries where such materials are required to further the war program.

In a more positive way, the Office of Imports directs the Board's

activities with respect to the mineral-procurement program.

Office of Imports.—The record of achievement in the foreign mineral program established by the Reconstruction Finance Corporation subsidiaries terminated, as already outlined, on February 25, 1943. Thereafter—except for banking and warehousing responsibilities retained by the Reconstruction Finance Corporation—the Office of Imports, Board of Economic Warfare, assumed responsibility for the negotiation, preparation, supervision, and administration, both in the United States and abroad, of all existing or future imported-materials contracts financed by the Reconstruction Finance Corporation, including development, preclusive operations, and related activities. However, all negotiations abroad are conducted in complete accordance with the provisions set forth in the statement of the President dated May 20, 1942, relating to established prerogatives of the United States Department of State.

### UNITED STATES DEPARTMENT OF STATE

As the principal responsibility of the Department is to determine policies of this Government in its relation to international problems, it participates actively in the war program with respect to the procurement of essential materials from foreign countries and assumes its obvious prerogatives in connection with the longer-range postwar

economic planning program.

The Executive orders heretofore mentioned, which created the several subsidiary companies of the Reconstruction Finance Corporation and the Board of Economic Warfare, provided for foreign representation of these agencies by technically trained mining experts (engineers, geologists, and ore buyers), whose duties have been confined more or less to their specialized fields. In most foreign countries where the United States has negotiated for the purchase of essential minerals (this is especially true in Latin America), preliminary transactions and final contracts with producers have been facilitated and concluded through the intermediary of some Government agency of the country involved. Thus the State Department of necessity par-

ticipated in the negotiations by procurement agencies of the United States Government whose direct responsibility has been acquisition of Although the Metals Reserve Co. did negotiate strategic materials. a 5-year contract with Bolivian tin producers in November 1940 and about the same time concluded arrangements for substantially the entire copper production of Latin America, this Government in 1941 began active negotiations with the principal American republics for over-all agreements whereby the exportable surplus of all their strategic materials would be made available to the United States. Rigid export-control systems by producing countries obviously were essential and constituted one of the principal obstacles finally surmounted in the successful negotiations of four over-all Governmentto-Government agreements concluded during 1941, three of which were in operation during 1942 with Brazil, Mexico, and Chile; a Peruvian agreement expired in September 1942, and, although negotiations for a new agreement were begun later in the year, no conclusive arrangement was reached by the beginning of 1943. Separate agreements were also in effect throughout 1942 between United States Government buying agencies and individual producers of certain minerals in Argentina and Colombia.

Throughout all these negotiations, the United States Department of State maintained close contact with all agencies involved and retained its over-all responsibility for coordinating activities and efforts of the representatives of other agencies of this Government engaged in commercial or economic work within any particular country. The Bureau of Mines, by a cooperative arrangement with the State Department, provided technical assistance throughout 1942;

The second secon

details are covered later in this summary.

To assist the Petroleum Coordinator for War and other war agencies in collecting current information relating to the petroleum situation in key producing countries of Latin America, the State Department employed specialists and assigned them to certain American embassies.

### UNITED STATES DEPARTMENT OF THE INTERIOR

Geological Survey.—The foreign work of the Survey has been confined to Latin America, where it has participated since 1940 in the cultural relations program sponsored and financed through the United States Department of State. The plans and modes of handling the projects and problems involved have been approved by that Department and the foreign governments concerned before the assignment of geologists, usually specialists in certain strategic minerals. During the fiscal year 1942 Survey geologists made detailed studies in Cuba, Mexico, and Brazil, and reconnaissance studies in Honduras and Costa Rica. During the fiscal year 1943 investigations were conducted in Cuba, Mexico, Brazil, and Central America, and additional projects were developed in Panama and Argentina. Both the War Production Board and the Board of Economic Warfare have benefited by the work of the Survey.

Bureau of Mines.—Because information regarding the mineral resources of Latin America was inadequate and urgent need for such data was anticipated, the Bureau in 1939 assigned one mining engineer to the area to collect such material. During the next 2 years comprehensive reports were compiled relating to the mineral production and trade of Bolivia, Peru, Chile, Argentina, Brazil, Uruguay, and Paraguay. During this period, officials of American embassies in the

several countries of Latin America were confronted with an everincreasing number of problems and projects relating to mining, precipitated by the national defense program of this Government. need for reliable technical aid to enable the several embassies to function more efficiently was evident, and the Bureau of Mines assumed responsibility for assigning mining engineers to serve as technical advisers to American embassies in Argentina, Brazil, Chile, Bolivia, Peru, and Mexico; this arrangement was in effect until July 1, 1942. The impetus of our entry into the war, with particular reference to this country's need for increased mineral supplies, resulted in the almost immediate assignment of mining engineers, geologists, and buyers throughout Latin America in particular, as well as in South Africa, Belgian Congo, and Australia, by the two agencies of this Government directly responsible for the mineral-procurement program, namely, Metals Reserve Co. and the Board of Economic War-Early in 1942 the United States Department of State, empowered by special authorization to employ technical experts, created a mineral attaché service as a segment of its Auxiliary Foreign Service and on July 1, 1942, assumed administrative responsibility for the Bureau's foreign mineral specialists, who were already serving as technical advisers to our several American embassies afore-mentioned. cooperative arrangement between the Bureau of Mines and the State Department has placed responsibility on the former for the technical supervision and direction of these mineral attachés. Coincidental with this arrangement, the Bureau has proposed for early adoption a plan whereby it will assume responsibility for more active participation in the economic studies conducted by this Government which may serve as basic data essential in the planning of international economic policy for the postwar period.

### OTHER FEDERAL AGENCIES

Other than joint economic committees and raw materials boards composed of representatives of the United States and other United Nations (of which several were created during 1942 to develop maximum utilization of their combined resources in the production of war requirements), a few Federal agencies of importance in the war program were in operation during the year whose functions and responsibilities have had a direct influence on the foreign mineral investigations of those establishments afore-mentioned, although they did not participate actively in field activities.

War Production Board.—Established within the Office for Emergency Management by Executive Order 9024 of January 16, 1942, this Board has exercised direction over the entire war production and procurement program. Its recommendations have served as operating instructions covering the mineral commodities and tonnages of each to be purchased abroad and imported by the United States to

insure maximum production of munitions.

Office of the Coordinator of Inter-American Affairs.—Soon after its establishment on July 30, 1941, by Executive Order 8840, this agency developed a program for assisting other American republics by providing technical aid to mining agencies of such Governments. Groups of mining engineers had been assigned to Brazil and Peru early in 1942, when the Board of Economic Warfare assumed over-all responsibility for similar activities; in consequence, these particular functions and

the personnel involved were transferred to the Board of Economic Warfare in May 1942.

Miscellaneous.—Other agencies, such as the Office of Strategic Services (a unit of the combined Chiefs of Staff, United States and Great Britain, established on February 6, 1942), the Office of Censorship, established by Executive Order 8985 of December 19, 1941, the Army-Navy Munitions Board, and the Intelligence Services of War and Navy Departments established commodity research units to analyze foreign mineral data. Major economic research and statistical agencies, such as the United States Tariff Commission and the Bureau of Foreign and Domestic Commerce, by special arrangements with the Board of Economic Warfare directed most of their activities toward meeting the requirements of the Board.

### OBJECTIVES OF RESEARCH

The vast increase in the volume and character of foreign technical, economic, and statistical research relating to one phase or another of mining developed during 1942 by the Federal Government had as its preliminary objective attainment, as quickly as possible, of maximum production and procurement of the raw materials essential to the United States and other United Nations in conducting the global war against the Axis Powers. Of secondary but not minor significance is the definite need for these accumulated data in postwar economic planning programs, some ideas of which were manifest during 1942 but which early in 1943 received considerable impetus probably as a result of the military successes of the Allies in the North African and Mediterranean areas. In this connection, many plans and suggestions have been advanced that contemplate international action of one kind or another with reference to mineral production and distribution, as well as the equitable commercial and political control of mineral resources among the nations of the world. Most of the plans suggested thus far appear to stem from a desire to make effective article 4 of the Atlantic Charter, which reads-

They will endeavor with due responsibility for their existing obligations, to further the enjoyment by all States, great or small, victor or vanquished, of access on equal terms to the trade and to the raw materials of the world which are needed for their economic prosperity.

Some ideas of the trend of thought in this direction may be gleaned from the following references:

Feis, Herbert (adviser on international economic affairs, U. S. Department of State). Raw Materials, War and Post-war. Dept. of State Bull., vol. 8, No. 200, April 24, 1943, pp. 339-347.

Division for the Social and International Relations of Science. Mineral Resources and the Atlantic Charter. Trans. of conference held July 24-25, 1942; pub. by British Association for the Advancement of Science, Burlington House, London, W. 1, in Advancement of Science, vol. 2, No. 7, October

1942, pp. 187-253.

LEITH, C. K., FURNESS, J. W., AND LEWIS, CLEONA. World Minerals and World Peace. Brookings Inst., Washington, January 1943, 253 pp.

CORBETT, PERCY E. Post-war Worlds. Inst. Pacific Relations, New York, 1942,

211 pp.

# STATISTICAL SUMMARY OF MINERAL PRODUCTION

(GENERAL UNITED STATES SUMMARY AND DETAILED PRODUCTION BY STATES)

By Martha B. Clark and Marian E. Meyer

### SUMMARY OUTLINE

	Page		Page
Introduction		General tables	37
Unit of measurement	35	State tables	49
Elimination of duplication	35	1	 

### INTRODUCTION

This report continues the series of annual statistical summaries published in previous years as chapters of Mineral Resources and Minerals Yearbook.

### UNIT OF MEASUREMENT

The unit of measurement used by the Bureau of Mines for each mineral product in reports on the mineral resources is that common to the industry concerned, and the variation in these units makes it impracticable, if not impossible, directly to combine and compare the different minerals except as to value. Although most of the products are measured by weight, some are measured by volume and some by number of "pieces," etc.; for some no total quantity figures are available.

### ELIMINATION OF DUPLICATION

In the totals for the United States, shown in the following "general" tables, duplication has been eliminated wherever practicable, and in the State totals given in the State tables virtually all duplication has been eliminated. For instance, in both general and State tables the output of coke is shown but its value is not included in the totals. as the value of the coal used in its manufacture enters into the value of the coal production which is included in the totals. For asphalt, both native and oil are shown in the general tables, but the value of the oil asphalt is excluded from the totals as it duplicates that of the petroleum from which it is manufactured. For the clay industries, no figures have been available for total clay produced. For years before 1936, the total value of clay products is included in both general and State totals as representing the first marketable form of the greater part of the clay produced; the quantity and value of the clay mined and sold in the raw state by miners to users of clay are shown separately also, but the value is not included in the totals as it is duplicated largely in that for clay products. For years beginning with 1936, as the Bureau of Mines believes that a closer approach to the value of domestic clay in its first marketable form results from the inclusion of the value of clay sold by producers and of clay products other than pottery and refractories, the United States and State

totals include such values for the clay industries. This change in practice should be borne in mind when comparing the values beginning

1936 with those for earlier years.

United States totals.—In the general tables both iron ore and pig iron are shown, but the value of the pig iron rather than the iron ore is included in the United States totals, as that is considered the better means of presenting the statistics for iron in its first marketable form. For gold, silver, copper, lead, and zinc the value of "smelter output" is included in the general totals, and to account more fully for the value of the ores treated these smelter figures are supplemented by the value of the byproduct sulfuric acid. The value of pigments (white lead, red lead, lithopone, litharge, and orange mineral) manufactured from metals is not included in the general tables, as the base from which they are made is included in the output of lead or zinc, whereas the value of sublimed blue lead, sublimed white lead, leaded zinc oxide, and zinc oxide is included, as these are made in large part direct from the ores and do not enter into the lead or zinc totals, which represent smelter output.

State totals.—In the State tables also iron ore and pig iron are both shown. As blast-furnace products cannot be traced to the States in which the ore is mined, the value of the ore is used in the State totals. For ores of gold, silver, copper, lead, and zinc no values are shown, and in fact none are recorded; instead, for each of these metals the recoverable content of the ores is used as the basis of valuation. The value of the zinc and lead pigments is not included in the State total, as the recoverable zinc and lead content of the ores from which the products were made is included under zinc or lead. The value of the sulfuric acid produced as a byproduct of copper and zinc smelting and zinc roasting is not included in the State total, as tracing this product back to the State producing the ore has not been possible.

GENERAL TABLES

Mineral products of the United States, 1940-421

Product	194	0	19	41	1942	
Froduct	Quantity	Value	Quantity	Value	Quantity	Value
METALLIC						
Lluminum short tons (2,000 pounds) untimonial lead do untimony:	206, 280 4 29, 762	\$75, 292, 000 (4)	(2 <sup>3</sup> ) 4 40, 237	(2 3) (4)	(2 3) 4 51, 762	(2 8) (4)
Metal do do Ore and concentrates do do	(5)	(5)	(2 5)	(2 5) (2 3)	(2 5)	(2 5)
Bauxite	1, 124 487, 186	72, 900 2, 578, 968	(2 3)	(2 3) (2 3)	(2 3) (2 3)	(2 3) (2 3)
Beryllium concentratesdo	121	3, 721	158	\$7, 300	(2 8)	(2 3)
Metal pounds	6, 467, 260	4, 527, 082	7, 044, 417	5, 498, 404	(2 8)	(2 8)
In compounds do Dhromite short tons	205, 900 2, 982	144, 130   28, 784	265, 700 (2 3)	207, 246	(2 3) (2 3)	(2 8) (2 8)
Copper, sales value do do do	909, 084 1, 292, 660	205, 453, 000 128, 127, 810	966, 072	227, 993, 000	1, 087, 991	7 \$256, 766, 00
fold 8troy ounces	6, 003, 105	210, 108, 700	5, 976, 419	209, 174, 600	(2 3) 3, 741, 806	(2 3) 130, 963, 210
ron: Ore <sup>6</sup> short tons_	84, 221, 854	189, 086, 799	104, 220, 473	9 249, 705, 903	118, 707, 133	9 279, 178, 75
Pigdo	46, 958, 929	840, 442, 032	55, 223, 641	1, 111, 811, 316	59, 100, 601	1, 227, 389, 68
ead (refined), sales valuedodododo	433, 065 12, 823, 633	43, 307, 000 10 3, 462, 380	470, 517	53, 639, 000	467, 367	7 58, 888, 00
Agnesium (new ingot) pounds  Angnesium (new ingot) pounds  Angnese ore (35 percent or more Mn) short tons  Angnaniferous ore (5 to 35 percent Mn) do	44, 936	1, 169, 024	(2 8)	(2 3)	(2 3)	(2 3)
Aercury:	1, 272, 932	3, 348, 042	(2 3)	(2 3)	(2 3)	(2 3)
Metal	37, 777	6, 681, 618	(2 3) (11)	(2 3) (12)	(2 3) (11)	(2 3)
folybdenumpounds_	25, 329, 000	17, 189, 000	(2 8)	(12) (2 3)	(23)	(12) (2 3)
Vickelshort tonsshort tons	554	(18)	(2 3)	(2.3)	(2 8)	(2 8)
Copper do Dry and siliceous (gold and silver) do	69, 278, 000	(12)	78, 453, 000	(12)	92, 664, 000	(12)
Dry and siliceous (gold and silver)dodo	18, 700, 000 6, 144, 000	(12)	17, 639, 000 6, 151, 000	(12) (12)	11, 649, 000 7, 612, 000	(12) (12)
Lead-copperdo	10,000	(12)	6,000	(12) (12)	1, 012, 000	(12)
Zincdodo	9, 521, 000 79, 000	(12) (12)	10, 492, 000 81, 000	(12) (12)	9, 155, 000	(12) (12)
Zinc-lead do	12, 866, 000	(12)	16, 211, 000	(12)	7, 000 18, 827, 000	(12)
Zinc-lead-copperdo	4, 000 47, 339	(12) 1, 986, 000	(2 8) 1,000	(12) (2 8)	2, 000 (2 3)	(12) (2 3)

# Mineral products of the United States, 1940-42-Continued

	194	1940		41	1942	
Product	Quantity	Value	Quantity '	Value	Quantity	Value
METALLIC—continued						
elenium pounds	368, 709	(13)	681, 650	(13)	316, 613	(13)
eleniumpounds ilver <sup>14</sup> troy ounces	69, 585, 734	\$49, 483, 189	72, 336, 029	\$51, 438, 954	56, 090, 855	(18) \$39, 886, 83
antalite-columbitepounds[			239, 983 (2 3)	219	(2 3)	(2 3)
elluriumdo	88, 996	(13)	239, 983	(13) (2 3)	98, 798	(13) (2 3)
'in (metallic equivalent)short tons	55	54, 900	(2 3)	(2 3)	(2 3)	(2 3)
'itanium concentrates:						
Ilmenitedo	20, 702	183, 686	21, 526	196, 522	(18)	(13)
Rutiledo	2, 657	393, 243	3, 431	493, 782	2, 649	410, 95
'ungsten ore (60-percent concentrates)do	5, 319	6, 576, 318	(2 3)	(2 8)	(2 3)	(2 3)
anadiumpounds_inc, sales valueshort tons_	2, 162, 916	1, 044, 100	(2 3)	(2 3)	(2 3)	(2 8)
inc, sales valueshort tons	589, 988	74, 338, 000	652, 599	97, 890, 000	629, 957	7 109, 613, 00
ther metallic 18		1, 192, 471		2, 031, 953		3, 641, 91
Total value of metallic products (approximate)		1, 678, 600, 000		2, 132, 000, 000		2, 361, 800, 00
			<del></del>			
rsenious oxideshort tons	23, 339	561, 300	34, 784	1 110 000	(2 16)	(2 16)
sbestos do	20, 060	674, 508	(2 16)	1, 119, 320	(2 16)	(2 16)
sphalt:	20,000	074, 008	(*.9)	(* .9)	(- 10)	(* .0)
Sphan.	500, 281	2, 766, 240	691, 168	3, 169, 193	975, 373	4, 279, 4
Native do Oil (including road oil)	5, 262, 959	41, 398, 735	(29)	(2 9)	(3 9)	(2 9)
Sarite (crude)	409, 353	2, 596, 743	503, 156	3, 134, 234	429, 484	2, 673, 0
Gron minerals do	243, 355	5, 643, 390	301, 282	6, 785, 662	226, 723	5 733 6
Promine pounds	59, 266, 275	11, 772, 515	68, 317, 019	11, 506, 213	65, 880, 935	5, 733, 6 13, 729, 3
alcium-magnesium chloride (75 percent CaCl <sub>2</sub> ) short tons	99, 536	998, 241	165, 932	1, 333, 370	224, 527	1, 733, 1
roninepounds_ alcium-magnesium chloride (75 percent CaCl <sub>2</sub> )short tons_ ementbarrels (376 pounds net)	132, 864, 383	193, 464, 869	170, 365, 440	250, 589, 481	187, 809, 208	286, 905, 1
llov.						
Products (other than pottery and refractories)		17 114, 000, 000		17 135, 000, 000		17 115, 000, 0
Products (other than pottery and refractories)short tons	4, 700, 951	18, 162, 485	7, 018, 056	24, 925, 717	7, 342, 843	24, 523, 2
oal:					la di Silandi I	
Bituminous 18do	19 460, 771, 500	19 879, 327, 227	<sup>19</sup> 514, 149, 245	19 1, 125, 362, 836	19 580, 000, 000	19 1, 360, 219, 0
Pennsylvania anthracitedo	51, 484, 640	205, 490, 000	56, 368, 267	240, 275, 000	60, 327, 729	271, 673, (
oke 9dodo	57, 072, 134	273, 832, 410	65, 186, 578	9 352, 967, 237	70, 568, 944	9 425, 613, 7
iatomitedo	(20)	(20)	(20)	(20)	(20)	(20)
mery do eldspar (crude) long tons (2,240 pounds) luorspar short tons	1,046	9,349	4,876	42, 484	5,277	49, 4
eldspar (crude)long tons (2,240 pounds)	290, 763	1,271,995	338, 860	1, 519, 456	307, 823	1, 516, 7
iuorsparsnort tons	233, 600	4, 744, 808	320, 669	6, 724, 782	360, 316	8, 897, 7
uller's earthdo	146, 568	1, 471, 083	207, 446	2, 111, 674	204, 244	2, 139, 6 299, 9
tarnet for abrasive purposesdodotems and precious stones	4,716	259, 345	5, 501	371, 752	4,357	(21)

		and the second second		in a constitution of the		
Graphite:	(00)	(00)	(2 16)	(2 16)	(2 16)	(2 16)
Amorphousshort tons	(20)	(20)	(2 16)	(2 16)	(2 16)	(2 16)
Crystalline pounds Grindstones and pulpstones short tons						
Grindstones and pulpstones Short tons	13, 323	496, 448	15, 536	545, 556	14,681	539, 739
Campaign (omida)	3, 699, 015	5, 227, 910	4, 788, 534	6, 794, 223	4, 697, 568	6, 811, 180
Gypsum (crude)do Heliumcubic feet	22 9, 450, 855	22 85, 061	(20)	(20)	(20)	(20)
Helium	(20)	(20)	(20) (20)	(20) (20)	(20)	(20)
Iodinepounds	(20)	93,716	8, 335	175, 581	8,708	190,750
Kyaniteshort tons	4, 241	93,710	0,000	40 041 100	6, 103, 791	44, 367, 441
Lime do	4, 886, 929	33, 956, 385	6, 079, 416	42, 941, 162		44, 507, 441
Tithium minerals	2,011	80, 679	3,832	115, 718	5,405	243, 516
Magnesite (crude)do Magnesium compounds (natural) (including brucite)pounds_	333, 166	2, 487, 969	374,799	2, 655, 547	497, 368	3, 874, 334
Magnesium compounds (netural) (including bruelta) nounds	216, 532, 000	2, 452, 814	274, 714, 000	3, 587, 784	738, 514, 000	10, 727, 560
Magnesium compounds (natural) (metating bracket)	210,002,000	-, -, -, -, -, -, -, -, -, -, -, -, -, -		*** ** ** ****************************		
Marl:  Calcareous short tons	25, 516	42, 481	183, 009	175, 393	194, 878	135, 046
Calcareoussnort tons.		389, 888	11, 120	619, 664	10, 110	448, 440
Greensanddo	6, 697	209, 200	11, 120	- 010,004	10, 110	110, 110
Mica:		1.1.1.1.1	(2 16)	44.40	(2 16)	(2 16)
Scrapdodo	22, 386	314, 565		(2 16)	(3.10)	
Sheetpounds	1, 625, 437	291, 685	(2 16)	(2 16)	(2 16)	(2 16)
Millstones	1 7 7	6, 558		15, 579	l1	10, 391
Mineral pigments:						
Mineral pigments:					. 1	
Natural pigments and manufactured iron oxide pigments	(00)	(92)	(23)	(23)	97, 327	7, 764, 232
Zinc and lead pigments 4. short tons  Mineral waters gallons sold  Natural gas M cubic feet	(23) 164, 775	19, 334, 347	228, 123	( <sup>23</sup> ) 27, 994, 694	156, 215	21, 255, 125
Zinc and lead pigments *		19, 554, 547	(21)	(21)	(21)	(21)
Mineral watersgailons sold	(21)	(2í)				711, 738, 000
Natural gas M cubic feet.	2, 660, 222, 000	577, 939, 000	2, 812, 658, 000	621, 333, 000	3, 055, 000, 000	711, 738, 000
			1 4 4			
Natural gasoline and cycle productsgallons	2, 339, 400, 000	68, 261, 000	2,688,714,000	105, 815, 000	2, 708, 034, 000	102, 000, 000
Time and not playing and of the production of the state o	Z, cin	(11)	707, 196, 000	13, 305, 000	801, 780, 000	19, 000, 000
Liquefied petroleum gases do do Oilstones, etc short tons	(11) (20)	(20)	(20)	(20)	(20)	(20)
Olistones, etcshort tons	2, 500	15, 000	4, 828	24, 401	5, 739	45, 201
Olivinedo	2,000	10,000	86, 503	657, 556	71, 500	516, 887
Peatdodo	70, 097	516, 865	80,000		1 007 470 000	1, 620, 000, 000
Petroleumbarrels (42 gallons)	1, 353, 214, 000	1, 385, 440, 000	1, 402, 228, 000	1, 602, 000, 000	1, 385, 479, 000	1, 020, 000, 000
Phosphate rock long tons	4,002,700	12, 334, 662	4, 689, 652	15, 596, 273	4, 644, 240	16, 597, 492
Phosphate rock long tons. Potassium salts short tons	25 393, 058	12, 562, 050	26 531, 346	17, 368, 237	25 680, 831	22, 962, 518
Pumicedo	82, 407	449, 914	117, 310	669, 514	126, 522	706, 199
long tons	626, 640	1, 920, 000	645, 257	2, 009, 000	720, 363	2, 464, 000
Pyrites long tons Salt (sodium chloride) short tons	10, 359, 960	26, 474, 619	12, 720, 629	33, 620, 376	13, 693, 284	38, 144, 234
Balt (sodium chioride)short tons	10, 305, 500	20, 111, 010	12, 120, 020	00, 020, 010	20, 500, 201	00, 110, 101
Sand and gravel:	0 770 744	4 001 700	0 477 111	0 110 500	3, 622, 487	6, 784, 427
Glass sanddodo	2, 759, 544	4, 881, 508	3, 475, 111	. 6, 113, 529		181, 716, 000
Sand (molding, building, etc.) and graveldo	235, 548, 000	105, 806, 000	285, 240, 000	141, 093, 000	300, 724, 000	
Sand (molding, building, etc.) and gravel dodo	26 104, 519	26 1, 174, 044	(26)	(26)	(26)	(26)
Silica (quartz)short tons_	31, 865	176, 390	41,685	228, 587	65, 878	331, 494
Clark (quarte)		5, 738, 269	618, 660	7, 515, 634	590, 770	6, 360, 223
Slatedo Sodium salts (carbonates and sulfates) (natural)do	317, 267	3, 157, 916	304, 201	3, 266, 123	325, 652	3, 815, 272
Sodium saits (cardonates and sulfates) (natural)do	159 799 040	160, 044, 115	183, 107, 960	195, 337, 426	195, 884, 490	205, 002, 019
Stone 27do	153, 733, 040				3, 128, 559	50, 100, 000
Sulfurlong tons	2, 558, 742	40, 900, 000	3, 401, 410	54, 400, 000		8, 253, 104
Sulfurio acid (60° Rauma) (hyproduct)28 short tons	840, 937	6, 797, 421	915, 989	7, 201, 161	960, 764	
Tale, pyrophyllite, and ground soapstone 27do	281, 375	3, 008, 320	416, 369	4, 701, 892	387, 963	4, 754, 076
Tripolidodo	30, 212	366, 569	29, 301	421,746	17, 536	272, 428
1110011			,			

### Mineral products of the United States, 1940-42—Continued

	1940		194	11	194	1942	
Product	Quantity	Value	Quantity	Value	Quantity	Value	
Vermiculiteshort tons	22, 299	\$137, 698 2, 806, 861	23, 438	\$125, 444 4, 457, 215	57, 848	\$319, 931 4, 257, 086	
Total value of nonmetallic products (approximate)		3, 935, 300, 000		4, 746, 000, 000		5, 207, 700, 000	
Total value:  Metallic		1, 678, 600, 000		2, 132, 000, 000		2, 361, 800, 000	
Nonmetallic: Fuels Other Other		3, 116, 500, 000 818, 800, 000		3, 708, 100, 000 1, 037, 900, 000		4, 084, 600, 000 1, 123, 100, 000	
Grand total approximate value of mineral products		5, 613, 900, 000		6, 878, 000, 000		7, 569, 500, 000	

<sup>1</sup> In this general statement certain of the figures represent shipments rather than quantity mined, and some of the figures for 1942 are subject to revision. For details see following chapters of this volume.

 Figures withheld from publication at request of Committee for War Information.
 Value included in total value of metallic products.
 Figures represent antimonial lead produced at primary refineries from both domestic and foreign primary and secondary sources; no figures for value of antimonial lead available. Estimate of value of primary antimony and lead contents of antimonial lead from domestic sources included in total value of metallic products.

<sup>5</sup> Largely from foreign ore; value not included in total value.

6 Product from domestic ores only.

<sup>7</sup> Value does not include premiums paid to miners by the Government. Total premiums for copper, lead, and zinc amounted to approximately \$22,500,000. 8 According to Bureau of the Mint. Valued at \$35 per ounce.

Value not included in total value.

10 Value calculated at nominal price-27 cents per pound.

11 Figures not available.

12 Figures showing values not available.

13 Value included in total value of metallic products: Bureau of Mines not at liberty to publish figures.

14 According to Bureau of the Mint.

- 15 Includes value of following products. Figures are shown wherever Bureau of Mines is at liberty to publish them.
- 1940: Bismuth, cobalt, iron ore sold for paint (9,981 short tons, \$45,578), and thallium.

  1941: Bismuth, cobalt, indium, iron ore sold for paint (23,287 short tons, \$101,710),
  radium, thallium, uranium compounds, and zircon (174 short tons, \$5,153)

  1942: Bismuth, cobalt, germanium, indium, radium, thallium, and zircon.

  10 Value included in total value of nonmetallic products.

  11 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941-42: Estimate by Bureau of Mines as no general canvass

by Bureau of the Census.

- 18 Includes brown coal and lignite, and anthracite mined elsewhere than in Pennsylvania. 19 According to Bituminous Coal Division; value for bituminous includes selling
- expenses. Figures for 1942 are preliminary.

  20 Value included in total value of nonmetallic products; Bureau of Mines not at liberty
- to publish figures. 21 No canvass. Estimate of value included in total value of nonmetallic products.
- Figures cover fiscal year ended June 30 of year stated.
   Canvass discontinued after 1915. Figures for iron ore sold for paint given in foot-

24 Sublimed blue lead, sublimed white lead, leaded zinc oxide, and zinc oxide. 25 Equivalent as K2O.

26 1940: Figures obtained through cooperation with Bureau of the Census; 1941-42;

No canvass by Bureau of the Census and no estimate made.

27 Figures for soapstone used as dimension stone included in figures for stone.

28 From copper and zinc smelters and zinc roasters and from roasting of high-sulfide gold and silver concentrates.

20 Includes value of following products. Figures are shown wherever Bureau of Mines is at liberty to publish them.

1940: Andalusite, crude aplite, natural sulfonated bitumen, chats (3,786,906 short tons, 1940: Andatuste, crude aplite, natural suitonated blumen, chast (3,785,905 soft tons, \$72,739), dumortierite, flint lining for tube mills, pebbles for grinding, silica sand and sandstone (ground) (342,218 short tons, \$2,088,314), strontium minerals (2,343 short tons, \$41,442), and sulfur ore (280 long tons, \$3,203).

1941: Andalustie, crude aplite, natural suitonated bitumen, chast (5,291,491 short tons, \$87,940), dumortierite, flint lining for tube mills (3,411 short tons, \$54,216), pebbles for

grinding (13,561 short tons, \$221,826), silica sand and sandstone (ground) (487,665 short tons, \$3,073,730), strontium minerals (4,724 short tons, \$69,054), and sulfur ore (409 long tons, \$2,553).

1942: Andalusite, crude aplite, natural sulfonated bitumen, dumortierite, flint lining for tube mills (2,576 short tons, \$49,967), pebbles for grinding (15,487 short tons, \$245,794), silica sand and sandstone (ground) (527,886 short tons, \$3,646,643), strontium minerals (4.041 short tons, \$55,529), and sulfur ore.

Value of mineral products of the United States, 1880-1942 1

Voor	Motolita		Nonmetallic		
Year	Metallic	Fuels 2	Other	Total	Grand total
880 1	\$190, 881, 000	\$120, 241, 000	\$56, 341, 000	\$176, 582, 000	\$367, 463, 00
881	192, 663, 000 219, 070, 000 201, 131, 000 182, 784, 000 174, 718, 000 204, 795, 000	149, 798, 000 170, 479, 000 185, 760, 000 165, 825, 000 183, 075, 000 184, 608, 000 217, 251, 000	60, 659, 000	210, 457, 000	403, 120, 00
882	219, 070, 000	170, 479, 000	63, 557, 000	234, 036, 000	453, 106, 00
884	102 704 000	185, 760, 000	61, 170, 000 58, 431, 000	246, 930, 000	448, 061, 00
883 884 885	174, 718, 000	183,075,000	61 758 000	244, 250, 000	407, 040, 000
886	204, 795, 000	184, 608, 000	61, 758, 000 66, 782, 000 77, 199, 000	224, 256, 000 244, 833, 000 251, 390, 000 294, 450, 000 311, 339, 000	419, 551, 00 456, 185, 00
887		217, 251, 000	77, 199, 000	294, 450, 000	535, 633, 00
888 889 890 891	242, 460, 000	201, 409, 000	79, 880, 000	311, 339, 000	535, 633, 00 553, 799, 00 542, 326, 00
800	250, 823, 000 303, 937, 000	208, 297, 000	83, 206, 000	291, 303, 000	542, 326, 00
891	280, 985, 000	230, 962, 000 237, 160, 000	80, 530, 000 82, 704, 000	311, 492, 000 319, 864, 000	615, 429, 00 600, 849, 00
892	284, 215, 000	248, 344, 000	89, 673, 000	338, 017, 000	622, 232, 00
893	223 654 000	251, 735, 000	70, 104, 000	321, 839, 000	545, 493, 00
894	187, 335, 000	235, 618, 000	127, 292, 000	362, 910, 000	550, 245, 00
894 895 896	248, 533, 000	235, 618, 000 268, 438, 000 268, 161, 000	125, 720, 000	394, 158, 000 388, 466, 000	642, 691, 00
897	252, 575, 000 270, 434, 000	208, 101, 000	120, 305, 000	388, 466, 000	641, 041, 00
898	308, 747, 000	267, 513, 000	150, 782, 000	381, 178, 000 418, 205, 000	727 042 00
899	484, 021, 000	253, 598, 000 267, 513, 000 340, 773, 000	127, 580, 000 150, 782, 000 185, 302, 000	526, 075, 000	1, 010, 096, 00
900	514, 232, 000	406, 376, 000	188, 328, 000	418, 295, 000 526, 075, 000 594, 704, 000	651, 612, 00 727, 042, 00 1, 010, 096, 00 1, 108, 936, 00
901	493, 814, 000	442, 409, 000	218, 855, 000	661, 264, 000	1, 155, 078, 00
902	605, 017, 000	469, 079, 000	253, 855, 000	722, 934, 000 906, 128, 000	1, 327, 951, 00
903	605, 017, 000 689, 253, 000 501, 314, 000 702, 785, 000 886, 280, 000 904, 151, 000	634, 226, 000	271, 902, 000	906, 128, 000	1, 495, 381, 00
904	702 785 000	602 252 000	273, 824, 000	857, 867, 000 920, 980, 000 1, 014, 600, 000	1, 359, 181, 00 1, 623, 765, 00 1, 900, 880, 00
905	886, 280, 000	652, 398, 000	362 202 000	1, 014, 600, 000	1, 023, 703, 00
107	904, 151, 000	789, 128, 000	376, 291, 000	1, 165, 419, 000	2, 069, 570, 00
908	000, 000, 000	584, 226, 000 584, 043, 000 602, 258, 000 652, 398, 000 789, 128, 000 716, 034, 000	273, 824, 000 318, 722, 000 362, 202, 000 376, 291, 000 324, 849, 000	1, 165, 419, 000 1, 040, 883, 000 1, 132, 015, 000 1, 237, 817, 000	2, 069, 570, 00 1, 591, 773, 00 1, 887, 107, 00
909	755, 092, 000	1 740, 204, 000	380, 811, 000	1, 132, 015, 000	1, 887, 107, 00
910	750, 027, 000 681, 023, 000	828, 213, 000 835, 763, 000	409, 604, 000 407, 295, 000	1, 237, 817, 000	1, 987, 844, 00 1, 924, 081, 00
912	862, 191, 000	945, 541, 000	430, 062, 000	1, 375, 603, 000	2, 237, 794, 00
911 912 913	879 058 000	1, 087, 843, 000	466, 644, 000	1, 554, 487, 000	2, 433, 545, 00
914	687 101 000	000 007 000	431, 234, 000	1, 424, 071, 000	2, 111, 172, 00
915	993, 353, 000	972, 617, 000	428, 674, 000	1, 401, 291, 000 1, 886, 310, 000	2 204 644 00
910 217	993, 353, 000 1, 622, 129, 000 2, 088, 914, 000	1, 332, 584, 000	1 553 726 (84)	1, 886, 310, 000	3, 508, 439, 00
915 916 917 918	2,000,914,000	2, 736, 151, 000	647 969 000	2,903,582,000	5 540 708 00
919	2, 156, 588, 000 1, 361, 099, 000	2, 510, 894, 000	751, 777, 000	3, 262, 671, 000	4, 623, 770, 00
920	1, 763, 675, 000	972, 637, 000 972, 617, 000 1, 332, 584, 000 2, 237, 837, 000 2, 736, 151, 000 2, 510, 894, 000 4, 192, 910, 000	665, 745, 000 647, 969, 000 751, 777, 000 1, 024, 755, 000	3, 384, 120, 000 3, 262, 671, 000 5, 217, 665, 000	3, 508, 439, 00 4, 992, 496, 00 5, 540, 708, 00 4, 623, 770, 00 6, 981, 340, 00
)21	654, 700, 000	2, 703, <del>4</del> 70, 000	780, 330, 000	3, 483, 800, 000	4, 138, 500, 00
922	988, 100, 000	2, 737, 880, 000	921, 310, 000	3, 659, 190, 000	4, 647, 290, 00
)23	1, 511, 930, 000	2 217 100 000	1, 157, 470, 000	4, 474, 570, 000	5, 986, 500, 00
924	1, 233, 370, 000	2, 898, 630, 000	1, 173, 800, 000 1, 236, 795, 000	4, 072, 430, 000	5, 305, 800, 00
25	1, 382, 155, 000	3, 058, 680, 000	1,236,795,000	4, 295, 475, 000	6 212 600 00
27	1, 220, 633, 000	3, 060, 047, 000	1, 200, 339, 000	4, 309, 367, 000	5, 530, 000, 00
926 927 928	1, 382, 155, 000 1, 405, 345, 000 1, 220, 633, 000 1, 288, 290, 000	3, 517, 100, 000 2, 898, 630, 000 3, 058, 680, 000 3, 541, 916, 000 3, 060, 047, 000 2, 884, 962, 000 3, 190, 527, 000	1, 266, 339, 000 1, 266, 339, 000 1, 249, 320, 000 1, 211, 948, 000 1, 216, 683, 000 1, 014, 510, 000 704, 410, 000	4, 295, 475, 000 4, 808, 255, 000 4, 309, 367, 000 4, 096, 910, 000 4, 407, 210, 000 3, 779, 010, 000	5, 637, 630, 00 6, 213, 600, 00 5, 530, 000, 00 5, 385, 200, 00 5, 887, 600, 00 4, 764, 800, 00
[29	1, 480, 390, 000 1	3, 190, 527, 000	1, 216, 683, 000	4, 407, 210, 000	5, 887, 600, 00
30	985, 790, 000	4, 102, 000, 000	1, 014, 510, 000	3, 779, 010, 000	4, 764, 800, 00
31 32	569, 790, 000 285, 875, 000	1, 892, 400, 000 1, 743, 400, 000	704, 410, 000	2, 596, 810, 000 2, 175, 825, 000	3, 166, 600, 00 2, 461, 700, 00
33	417, 065, 000	1, 683, 400, 000	432, 425, 000 454, 635, 000	2, 175, 825, 000	2, 461, 700, 00 2, 555, 100, 00
34	548, 934, 000	2, 233, 300, 000	543, 166, 000	2, 776, 466, 000	3, 325, 400, 00
34 35	733, 130, 000	2, 330, 000, 000	586, 870, 000	2, 916, 870, 000	3, 650, 000, 00
36	1, 081, 600, 000 1, 468, 200, 000	2, 759, 200, 000	716, 000, 000	3, 475, 200, 000 3, 945, 200, 000	4, 556, 800, 00
37 38	1, 468, 200, 000	3, 200, 500, 000 2, 820, 300, 000	744, 700, 000	3, 945, 200, 000	5, 413, 400, 00
39	892, 600, 000 1, 291, 700, 000	2, 820, 300, 000 2, 834, 300, 000	650, 300, 000 788, 200, 000	3, 470, 600, 000	4, 363, 200, 00 4, 914, 200, 00
40	1, 678, 600, 000	3, 116, 500, 000	818, 800, 000	3, 622, 500, 000 3, 935, 300, 000	5, 613, 900, 00
041	2, 132, 000, 000	3, 708, 100, 000	1, 037, 900, 000		
42 3	2, 132, 000, 000 2, 361, 800, 000	4, 084, 600, 000	1, 123, 100, 000	4, 746, 000, 000 5, 207, 700, 000	6, 878, 000, 00 7, 569, 500, 00

Figures for earlier years not available.
 Cond, natural gas, natural gasoline and allied products, petroleum.
 Subject to revision.

The sum of the following State totals does not reach the total for the United States given in the preceding table partly because figures for certain of the products included in the United States total are not available by States of origin. This fact is brought out in the opening text of this chapter and in the second table following.

In addition, there are many factors (the more important discussed in the opening text) that account for the disagreement between the sum of the State totals and the grand total for the United States, by products. Chief among these are: (1) The use of iron ore values in State totals and pig iron values in United States total; (2) the use of mine figures for gold, silver, copper, lead, and zinc in the State totals and mint and smelter figures (supplemented by the value of byproduct sulfuric acid from copper and zinc smelting and zinc roasting and the value of zinc and lead pigments made in large part direct from ores) in the United States total; and (3) the inclusion of estimates in the United States total for a few products for which no canvass has been conducted for many years and for which no estimate by States is made.

Many other less important differences are involved, but both State and United States totals are as complete and definite as seems possible with the data available. The practice is consistent from year to year, and it is believed that the reader can determine readily just what minerals are covered by the total concerned.

In every table each mineral produced is listed, and all figures are shown except those that the Bureau of Mines is not at liberty to publish.

						191	11-41 1	
State	1937	1938	1939	1940	1941	Total value	Rank	Percent of total for United States
Alabama Alaska Arizona Arrkansas Balifornia Olorado Domecticut Belaware District of Columbia Plorida Beorgia Adaho Illinois Indiana Owa Anasas Anasas Anasas Anasas Anasas Anine Afaryland Afaryland Afaryland Afaryland Afaryland Afaryland Afassachusetts Alichigan Alissispip Alissouri Alissouri Alissouri Alissouri Anasas Alissispip Alissouri Afontana Bebraska Bew Hersey Bew Jersey Bew Mexico Bew Versey Bew Mexico Bew York Borth Bor	27, 927, 958 94, 564, 494 25, 578, 393 476, 880, 693 476, 880, 693 38, 548 3, 689, 554 522, 687 13, 811, 958 12, 584, 060 40, 633, 119 54, 376, 403 127, 423, 680 182, 118, 905 4, 129, 391 10, 634, 854 17, 813, 345 119, 167, 573 152, 107, 070 4, 821, 950 52, 446, 272 82, 086, 815 4, 837, 816 1, 219, 869 31, 467, 931 72, 855, 748 17, 665, 874 11, 160, 441 2, 878, 4011	\$46, 296, 293 28, 796, 753 60, 756, 253 29, 395, 086 490, 108, 428 60, 369, 408 3, 059, 688 320, 621 568, 717 12, 866, 981 11, 598, 421 31, 738, 606 130, 155, 638 173, 738, 606 130, 155, 638 174, 892, 364 24, 794, 058 106, 654, 903 172, 306, 761 33, 548, 638 9, 407, 723 6, 666, 281 81, 380, 602, 547 4, 028, 712 27, 031, 281 1, 146, 606 24, 408, 545 63, 568, 953 73, 217, 439 14, 959, 228 2, 653, 473 104, 812, 581	\$52, 158, 173 25, 673, 566 75, 087, 930 29, 572, 632 467, 612, 196 64, 144, 557 4, 306, 351 13, 060, 453 14, 633, 655, 33, 138, 452 210, 798, 331 53, 884, 995 25, 170, 181 122, 959, 513 112, 840, 566 168, 903, 151 3, 769, 791 11, 781, 531 8, 242, 956 116, 088, 154 106, 455, 607 5, 192, 166 45, 633, 707 63, 343, 802 4, 390, 291 34, 670, 879 1, 187, 339 30, 441, 758 69, 987, 797 78, 409, 560 18, 533, 720 2, 689, 537 20, 681, 969	\$64, 998, 018 28, 724, 221 285, 291, 347 37, 479, 135 455, 672, 038 63, 188, 421 3, 914, 177 457, 326 640, 480 16, 932, 335 640, 799, 920 277, 943, 011 58, 975, 110 26, 006, 904 130, 859, 896 131, 974, 410 189, 153, 312 4, 374, 976 12, 605, 171 7, 573, 122 124, 774, 4581 128, 571, 690 7, 239, 646 79, 487, 873 4, 692, 146 42, 570, 529 1, 065, 373 2, 987, 381 63, 732 2, 987, 381 18, 655, 129	\$82, 730, 210 26, 809, 380 100, 472, 791 47, 081, 326 506, 796, 395 73, 960, 602 5, 284, 955 492, 631 700,000 19, 268, 779 21, 049, 261 45, 673, 740 320, 509, 559 80, 572, 397 21, 949, 261 45, 673, 740 320, 509, 559 80, 572, 397 171, 991, 685 169, 009, 195 228, 440, 044 4, 692, 448 17, 291, 523 9, 293, 169 142, 433, 673 178, 790, 274 17, 750, 726 61, 545, 052 86, 583, 460 6, 499, 070 46, 341, 010 1, 382, 506 11, 545, 052 86, 583, 460 61, 545, 052 86, 583, 460 86, 583, 460 87, 562 8	\$1, 680, 206, 000 2, 771, 051, 000 2, 771, 051, 000 2, 771, 051, 000 10, 229, 545, 000 112, 2946, 000 12, 377, 000 18, 915, 000 384, 296, 000 384, 296, 000 384, 244, 000 5, 648, 790, 000 2, 288, 780, 000 953, 953, 000 3, 128, 410, 000 3, 148, 031, 000 2, 471, 958, 000 130, 801, 000 3, 148, 000 3, 148, 000 130, 801, 000 2, 166, 995, 000 116, 531, 000 2, 166, 995, 000 116, 531, 000 2, 166, 995, 000 116, 531, 000 938, 200, 000 68, 017, 000 1, 941, 986, 000 2, 166, 995, 000 116, 531, 000 938, 200, 000 116, 531, 000 938, 200, 000 116, 531, 000 938, 200, 000 116, 531, 000 938, 200, 000 117, 000, 000, 000 2, 190, 528, 000 2, 190, 528, 000 257, 841, 000 75, 925, 000 5, 388, 654, 000	20 30 30 12 29 3 3 19 41 36 28 6 14 26 10 9 9 13 42 33 37 8 11 44 44 17 47 27 47 21 23 16 67	1.5 2.5 8.8 9.3 1.6 0.0 0.0 3.3 8.5 1.1 2.0 2.8 2.8 2.2 2.8 2.0 1.7 1.7 1.9 1.9 1.9 1.9 1.9 1.9 1.9 1.9 1.9 1.9

In this table iron ore, not pig iron, is taken as the basis of iron valuation, and for other metals mine production (recoverable content of metals) is the basis. State totals for 1942 not yet available. Comparable totals for years before 1911 not available.

# Value of mineral products of the United States, 1937-41, and total, 1911-41, by States-Continued

							na Pin	. 19	11-41	
	State		1937	1938	1939	1940	1941	Total value	Rank	Percent of total for United States
Oklahoma  Dregon Pennsylvania Rhode Island South Carolina South Dakota Pennessee Pexas Utah Permont Jirginia Washington West Virginia Wyoming			599, 817, 364 862,710 4, 022, 325 23, 472, 873 48, 893, 847 813, 290, 605 105, 652, 422 7, 042, 547 46, 019, 085 26, 658, 257 306, 590, 947 15, 239, 524	\$272, 860, 078 7, 536, 408 472, 773, 327 911, 599 4, 364, 034 23, 583, 359 32, 428, 512 740, 147, 465 59, 236, 355 6, 439, 552 42, 370, 169 21, 167, 004 254, 995, 309 10, 636, 741 37, 364, 363	\$236, 194, 064 8, 637, 047 531, 007, 890 980, 916 5, 422, 979 24, 813, 621 39, 818, 234 701, 972, 035 80, 127, 521 6, 972, 234 43, 902, 881 31, 595, 704 276, 084, 118 12, 704, 942 39, 413, 001	\$235, 535, 062 11, 229, 670 618, 347, 805 994, 997 5, 305, 597 23, 528, 825 42, 683, 407 725, 005, 009 104, 392, 989 6, 979, 772 50, 003, 672 28, 090, 188 329, 891, 960 13, 553, 688 43, 073, 533	\$263, 763, 923 12, 830, 176 737, 143, 530 1, 133, 400 7, 236, 503 24, 501, 696 56, 301, 592 868, 082, 690 122, 386, 473 8, 131, 670 71, 340, 932 425, 626, 303 17, 020, 722 52, 751, 354	\$9, 018, 834, 000 179, 224, 000 12, 362, 465, 000 28, 125, 000 88, 485, 000 380, 789, 000 1, 013, 272, 000 10, 977, 481, 000 2, 249, 987, 000 302, 595, 000 1, 077, 759, 000 606, 594, 000 8, 674, 276, 000 489, 892, 000 1, 294, 270, 000	4 40 1 48 45 35 25 2 15 38 24 31 5 32 22	8. 9 11. 3 10. 0 2. 0 7. 9

# Mineral products of the United States and principal producing States in 1941

Rank	Product	Principal producing States 1					
value	Troduct	In order of quantity	In order of value				
15	Aluminum	Tennessee, New York, Washington, North Carolina	Rank same as for quantity.				
101	Andalusite	Carfornia	D.				
(2)	Antimonial lead	Not separable by States	Not sanarable by States				
` <b>é2</b>	Antimony ore	l Idaho, Nevada, Alaska, Oregon	Idaho Alaska Mayada Montana				
83	Aplite (crude)	l Virginia	Rank same as for quantity.				
56	Arsenious oxide	Montana, Utah	Do.				
61	Asbestos	Vermont, Arizona, North Carolina, Georgia.	$\begin{bmatrix} \mathbf{D}_{0} \end{bmatrix}$				
- 1	Asphalt:	[	그렇게 살아보다는 사람들이 살아왔다면 그는 사람들이 가장 살아 보다는 사람들이 되었다면 살아 없었다.				
43	Native	Texas, Oklahoma, Kentucky, Alabama	Utah, Kentucky, Oklahoma, Texas.				
17	Oil	Not separable by States	Not separable by States.				
44	Barite (crude)	Missouri, Tennessee, Georgia, California	Missouri, Tennessee, Georgia, Arkansas.				
38	Bauxite	Arkansas, Alabama, Virginia, Georgia	Rank same as for quantity.				
97	Beryllium concentrates.	I South Dakota. New Hambanire Wyoming Maine	South Delrote Wroming New Homestine Marin				
55	Bismuth	I NOT Separable by States	South Dakota, Wyoming, New Hampshire, Maine. Not separable by States.				
99	Bitumen (natural sulfonated)	l IItah					
35	Boron minerals	California North Carolina, Texas, Michigan, California Not separable by States Michigan, West Virginia, California, Ohio Reported to the California California, Ohio Reported to California California, Ohio Reported to California California	Do.				
28	Bromine	North Carolina Tayas Michigan California	Michigan, North Carolina, Texas, California.				
37	Cadmium	Not separable by States	Not generalle her Ctates.				
52	Calcium-magnesium chloride	Michigan West Virginia Colifornia Ohio	Not separable by States.				
8	Cement.	Pennsylvania, California, New York, Texas	Rank same as for quantity.				
59	Chats	Oklahoma, Missouri, Kansas	Do. Missouri, Oklahoma, Kansas.				
74	Chromite	California, Oregon	- Missouri, Oklahoma, Kansas.				
12	Clay:						
13	Products (other than pottery and re- fractories).		Ohio, Pennsylvania, California, New York.				
25	Raw (sold by producers)	Pennsylvania, Georgia, Missouri, Ohio					
2	Coal:	remisylvania, Georgia, Missouri, Onio	Georgia, Pennsylvania, Kentucky, Missouri.				
-	Bituminous	TITLE TTE AT THE TOTAL TOTAL THE TOTAL TOT					
1	Dannaylyonia anthrosita		West Virginia, Pennsylvania, Kentucky, Illinois.				
71	Pennsylvania anthracite	Pennsylvania	Dank same as for anontity				
	Cobalt	Pennsylvania, Vermont, Nevada Pennsylvania, Ohio, Indiana, New York	. Do.				
5	Coke	Pennsylvania, Ohio, Indiana, New York	Do				
8	Copper	Arizona, Utah, Montana, Nevada	_  Do.				
46	Distoinite	I Callingnia (Jregon Navada Washington	l Do				
102	Dumortierite						
93	Emery	New York North Carolina, South Dakota, New Hampshire, Colorado Pannsylvania, New York, Wort Viverina, Okio,	.  Do.				
51	Feldspar (crude)	North Carolina, South Dakota, New Hampshire. Colorado	North Carolina, New Hampshire, South Dekote Coloredo				
10	Ferro-alloys	Pennsylvania, New York, West Virginia, Ohio North Carolina, Minnesota, Texas, Tennessee Kentucky, Illinois, New Mexico, Colorado Texas, Georgia, Florida, Illinois	Rank same as for quantity				
92	Flint lining for tube mills	North Carolina, Minnesota, Texas, Tennessee.	Minnesota, North Carolina Texas Tennessee				
36	Fluorspar	Kentucky, Illinois, New Mexico, Colorado	Illinois Kantucky New Movice Coloredo				
49	Fuller's earth	Tayes Georgia Florida Illinois	Don't some of for several to the Colorado.				

Rank of States in metal production (except aluminum, ferro-alloys, and pig iron) arranged according to mine reports, not smelter output. Separate figures for antimonial lead from primary sources not available.

# Mineral products of the United States and principal producing States in 1941—Continued

Rank	Posture	Principal produc	ing States
in value	Product	In order of quantity	In order of value
72 (³)	Garnet (abrasive) Gems and precious stones	New York, North Carolina, Vermont, Idaho	New York, North Carolina, Idaho, Vermont. No canvass for 1941.
77	GoldGraphite: Amorphous	Nevada	Rank same as for quantity.  Do.
66 34	Crystalline Grindstones and pulpstones Gypsum (crude)	New York, Alabama, Georgia, Washington Ohio, West Virginia, Washington New York, Michigan, Iowa, Texas	Do. Do. New York, Michigan, Nevada, Iowa.
87 88	HeliumIndium	Texas   Not separable by States   Not sepa	Rank same as for quantity.  Not separable by States.
68	Iodine (natural)	California  Minnesota, Michigan, Alabama, Pennsylvania  Pennsylvania, Ohio, Indiana, Illinois	Rank same as for quantity.  Minnesota, Michigan, Alabama, New York.
3 53 80	Pig Sinter Kvanite	Pennsylvania, Ohio, Indiana, Illinois Tennessee Virginia, California, North Carolina, Georgia	Rank samé as for quantity. Do. Virginia, North Carolina, Georgia, California.
19 21	Lead Lime	Missouri, Idaho, Utah, Oklahoma Ohio, Pennsylvania, Missouri, West Virginia	Rank same as for quantity. Do.
86 48 32	Lithium minerals	South Dakofa, California, North Carolina Washington, California, Nevada, Texas Michigan, Texas, California	Do. Do. Do.
41 47	Magnesium compounds (natural) Manganese ore Manganiferous ore	Michigan, Nevada, California, Texas Montana, Virginia, Arkansas, Georgia Minnesota, New Mexico, Nevada, Georgia	Michigan, California, Nevada, Texas. Rank same as for quantity. Minnesota, New Mexico, Montana, Nevada.
40 65	Manganiferous zinc residuum	New Jersey	Rank same as for quantity.
81 64 30	Calcareous Greensand Mercury	Michigan, Indiana, Virginia, Minnesota New Jersey California, Oregon, Nevada, Arkansas	Michigan, North Carolina, Wisconsin, Virginia. Rank same as for quantity. Do.
58	Mica Scrap	North Carolina, Georgia, Colorado, Virginia	North Carolina, Connecticut, New Hampshire, South Dakota.  North Carolina, Georgia, Virginia, South Dakota.
96 23	Sheet	North Carolina, New Hampshire, South Dakota, Connecticut Pennsylvania, Illinois, Kansas, Ohio	North Carolina, Connecticut, New Hampshire, South Dakota. North Carolina, West Virginia, New York, Virginia. Pennsylvania, Illinois, Kansas, Indiana.
(3) 24 4	Mineral waters	No canvass for 1941. Colorado, Utah, New Mexico, Arizona Texas, Louislana, California, Oklahoma	No canvass for 1941. Rank same as for quantity. Texas, California, West Virginia, Louisiana.
14	Natural gasoline and allied products: Natural gasoline and cycle products	Texas, California, Oklahoma, Louisiana	Rank same as for quantity.
69 85	Liquefied petroleum gases Nickel Oilstones, etc	Texas, Oklahoma, California, Illinois	Texas, California, Oklahoma, West Virginia. Not separable by States. Rank same as for quantity.
95	Olivine	Arkansas, Ohio, New Hampshire, Indiana North Carolina	Do.

(4)	Ores (crude), etc.:		
``	Copper	Utah, Arizona, New Mexico, Nevada	Value not eveilable
	Dry and siliceous (gold and silver)	Alaska, California, Nevada, South Dakota	Do.
	Lead	Missouri Idaho IItah Montone	l D-
	Lead-copper	Utah, Arizona, Idaho, and Colorado and Montana Oklahoma, Kansas, Tennessee, New Jersey	Do. Do.
	Zine	Oklahoma Kangag Tannaggaa Naw Jargay	Do. Do.
	Zinc-copper	Arizona	D0.
	Zinc-lead.	Arizona Oklahoma, Kansas, Idaho, Missouri	D0. D0.
•		Utah	Do. Do.
63	Peat	New York Illinois New Jorsey Michigan	Moine Non Non Year Tome Michigan
76	Pebbles for grinding	North Carolina Minneacta Daves Wissensin	Maine, New York, Iowa, Michigan.
ĭ	Petroleum	Toyon Colifornia Oklahama Illinaia	North Carolina, Minnesota, Wisconsin, Texas. Rank same as for quantity.
27	Phosphate rock	Utah New York, Illinois, New Jersey, Michigan North Carolina, Minnesota, Texas, Wisconsin Texas, California, Oklahoma, Illinois Florida, Tennessee, Montana, Idaho Alaska, California, Oregon, Montana New Mexico, California, Utah, Maryland California, Kansas, Nebraska, New Mexico Tennessee, California, Virginia, New York Not separable by States	Rank same as for quantity.
60	Platinum matala	Alaska California One at Africa	Florida, Tennessee, Idaho, Montana.
26	Potossium solts	Nort Movice California Titab Manalana	Rank same as for quantity.
62	Pumica	Colifornia Tomasa Nahasalaa Maryland	Do.
50	Direitos	Camornia, Kansas, Nebraska, New Mexico	California, New Mexico, Kansas, Nebraska.
89	Radium	Tennessee, Camornia, Virginia, New York	Rank same as for quantity.
22	Qol+	Not separable by States	Not separable by States. Michigan, New York, Ohio, Kansas.
12	Cond and manal	Michigan, New York, Ohio, Louisiana	Michigan, New York, Ohio, Kansas.
57	Sand and gravel	California, New York, Michigan, Illinois	California, New York, Pennsylvania, Ohio.
75	Gillian (greate)	Not separable by States Wisconsin, North Carolina, California, Tennessee	Not separable by States.
45	Silica (quartz)	Wisconsin, North Carolina, California, Tennessee	North Carolina, Wisconsin, California, Tennessee, Illinois, New Jersey, Ohio, West Virginia.
	Suica sand and sandstone (ground)	Illinois, New Jersey, Ohio, Pennsylvania Idaho, Montana, Utah, Arizona	Illinois, New Jersey, Ohio, West Virginia.
20 31	Bliver	Idaho, Montana, Utah, Arizona	I Rank same as for quantity.
42	DIBLO	<b> </b>	l Pennsylvania Vermont New York Virginia
42	Sodium salts (carbonates and sulfates)	California, Texas, Wyoming, Utah	Rank same as for quantity.
	(natural).		
11	Stone.	Pennsylvania, Michigan, Ohio, Illinois	Pennsylvania, Ohio, New York, Illinois.
90	Strontium minerals.	California, Texas, Washington	Rank same as for quantity.
18	Sulfur	Texas, Louisiana, California	Do.
88	Sulfuric acid from copper and zinc smelt- ers and roasters and from roasting of high-	Pennsylvania, Illinois, Arizona, Tennessee	Pennsylvania, Illinois, Arizona, Oklahoma.
	ers and roasters and from roasting of high-		
	sulfide gold and silver concentrates.		
100	Sulfur ore	Texas, Nevada, Colorado	Texas, Colorado, Nevada,
39	Talc, pyrophyllite, and ground soapstone 5. Tantalite-columbite	New York, North Carolina, California, Vermont	New York California Verment North Corolina
103	Tantalite-columbite	Wyoming	Rank same as for quantity.
73	Tellurium		Not separable by States.
94	Thallium	ldo	Do
91	<u>Tin</u>	Alaska, New Mexico, Alabama, South Dakota	Rank same as for quantity.
	Titanium concentrates:		
78	Ilmenite	Virginia, Florida	Do.
67	Rutile	Virginia, Arkansas, Florida	Do
70	Tripoli	Illinois, Missouri, Arkansas, Oklahoma	Do
29	Tungsten ore	California, Nevada, Idaho, Colorado	California Navada Colorado Idaho
79	Uranium compounds	Not canarable by States	Not consuchle has Otesten
54	Vanadium	Colorado, Idaho, Utah, Arizona	Colorado, Utah, Idaho, Arizona.
84	Vermiculite	Colorado, Idaho, Utah, Arizona Montana, Wyoming, North Carolina	Rank same as for quantity.
16			
98	Zircon	Florida, California	Do.
			J 104
	**************************************		

No canvass for 1941.

<sup>4</sup> Value not available.

<sup>\*</sup> Exclusive of soapstone used as dimension stone (all from Virginia), which is included in figures for stone.

### States and their principal mineral products in 1941 1

State	Rank	Percent of total value for United States	Principal mineral products in order of value
Alabama	18	1.47	Coal, iron ore, cement, stone.
Alaska	31	.48	Gold, platinum metals, coal, silver.
Arizona	14	1.79	Copper, gold, silver, zinc.
Arkansas		.84	Petroleum, coal, bauxite, natural gas.
California	3	9.03	Petroleum, natural gas, gold, cement.
Colorado	20	1.32	Coal, molybdenum, gold, silver.
Connecticut		.09	Stone, clay products, sand and gravel, lime.
Delaware	50	.01	Clay products, stone, sand and gravel, raw clay.
District of Columbia	. 49	.01	Clay products.
Florida	34	.34	Phosphate rock, stone, cement, sand and gravel.
FloridaGeorgia	33	.37	Raw clay, stone, cement, clay products.
Idaho	27	. 81	Lead, zinc, silver, gold.
Idaho Illinois Indiana	5	5. 71	Petroleum, coal, stone, cement.
Indiana	19	1.43	Coal, cement, petroleum, stone.
Iowa	29	. 51	Cement, coal, stone, clay products.
Kansas	9	3.06	Petroleum, natural gas, zinc, coal.
Kentucky	10	3.01	Coal, natural gas, petroleum, stone.
Louisiana	7	4.07	Petroleum, natural gas, sulfur, natural gasoline.
Maine	45	. 08	Stone, cement, sand and gravel, slate.
Maryland	37	. 31	Sand and gravel, coal, cement, stone.
Massachusetts	40	. 17	Stone, sand and gravel, clay products, lime.
Michigan	12	2. 54	Iron ore, petroleum, cement, salt.
Minnesota	8	3.18	Iron ore, manganiferous ore, sand and gravel, stone.
Mississippi	36	. 32	Petroleum, sand and gravel, natural gas, clay products.
Missouri	22	1.10	Lead, cement, stone, coal.
Montana	17	1.54	Copper, zinc, silver, gold.
Nebraska	43	. 12	Cement, petroleum, sand and gravel, stone.
Nevada	26	. 83	Copper, gold, silver, tungsten ore.
New Hampshire	47	. 02	Clay products, stone, sand and gravel, feldspar.
New Jersey	28	. 70	Zinc, clay products, sand and gravel, stone.
New Mexico	15	1.74	Petroleum, copper, potassium salts, natural gas.
New York	16	1, 63	Cement, petroleum, stone, sand and gravel.
New York North Carolina	35	. 34	Clay products, stone, bromine, sand and gravel.
North Dakota	46	. 06	Coal, sand and gravel, clay products, stone.
Obio	11	2.94	Coal, clay products, natural gas, lime.
Okahloma	6	4.70	Petroleum, natural gas, zinc, natural gasoline.
Oregon	39	. 23	Gold, stone, cement, sand and gravel.
Pennsylvania	2	13. 13	Coal, cement, natural gas, petroleum.
Rhode Island	48	. 02	Stone, sand and gravel, clay products, lime.
South Carolina	42	. 13	Stone, clay products, raw clay, sand and gravel.
South Dakota	32	.44	Gold, stone, cement, sand and gravel.
Tennessee	23	1.00	Coal, stone, cement, zinc.
Texas	1	15.46	Petroleum, natural gas, sulfur, natural gasoline.
Utah	13	2.18	Copper, gold, coal, silver.
Vermont	41	.14	Stone, slate, talc, asbestos.
Virginia	21	1.27	Coal, stone, sand and gravel, cement.
Washington	30	51	Coal, cement, gold, sand and gravel.
West Virginia	4	7.58	Coal, natural gas, petroleum, stone.
Wisconsin	38	.30	Stone, iron ore, sand and gravel, cement.
Wyoming		.94	Petroleum, coal, natural gas, natural gasoline.

#### Prices of gold, silver, copper, lead, and zinc, 1932-42 1

Year	Gold 2	Silver 3	Copper 4	Lead 4	Zinc 4
	Per fine ounce	Per fine ounce	Per pound	Per pound	Per pound
1932 1933	5 \$20. 67+		\$0.063	\$0.030 .037	\$0.030 .049
1934	25. 56 34. 95	.350 6.646+	.064	.037	.04
1935	35.00	71875	.083	.040	.04
1936	35.00	7745	.092	.046	.05
1937	35.00	7735	. 121	. 059	.06
1938	35.00	6.646+	. 098	. 046	. 04
1939	35.00	7.678+	.104	. 047	. 05
1940	35.00	8.711+	.113	. 050	. 06
1941	35.00	8.711+	.118	. 057	. 07
1942	35.00	8.711+	. 121	. 067	. 09

¹ Treasury legal coinage value of gold from Jan. 18, 1837, to Jan. 31, 1934, was \$20.67+ per fine ounce. For table of prices for silver, copper, lead, and zinc from 1850 to 1931, by years, see Mineral Resources, 1931, pt. 1, p. Al15.

² 1932- Legal coinage value; 1933-34: Yearly average weighted Government price; 1935-42: Price under authority of Gold Reserve Act of January 31, 1934.
² 1932-33: Average New York price for bar silver; 1934 and 1938-42: Treasury buying price for newly mined silver; 1935-37: Yearly average weighted Treasury buying price for newly mined silver.
⁴ Yearly average weighted price of all grades of primary metal sold by producers.
⁵ \$20.671835.

° \$0.64646464.

' \$0.67878787.

° \$0.71111111.

<sup>&</sup>lt;sup>1</sup> In this table iron ore, not pig iron, is taken as the basis of iron valuation, and for other metals mine production (recoverable content of metals) is the basis.

### STATE TABLES

### Mineral production of Alabama, 1940-41

Product	1940		1941	
Y	Quantity	Value	Quantity	Value
Aluminum short tons			(i.m.	
Asphalt (native)do	/1\		(1 2)	(1 2)
Asphalt (native) do Bauxite do do Gornario	2:3	1 32	(1)	(1)
Cement barrels	2 5 040 750	2 2 2 2 2 2 2	(1)	(1)
Clay:	<sup>3</sup> 5, 249, 759	3 \$7, 617, 405	<sup>3</sup> 7, 610, 030	3 \$11, 142, 649
Products (other than pottery and refractories)		4 2, 394, 000		4 2, 647, 000
Raw (sold by producers)short tons_	144, 354	143, 363		186, 476
Coal do do Coke do do Gold troy ounces.	<sup>5</sup> 15, 324, 163	5 35, 777, 923	<sup>8</sup> 15, 464, 523	5 41, 985, 942
Form ollows	4, 727, 378	2 13, 748, 837	4, 855, 062	2 18, 628, 534
Cold	45, 184	2 3, 422, 111	(1 2)	(1 2)
Good troy ounces.	5	175	30	1,050
Graphice, crystamnepounds_			(1)	(1)
Iron:	1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	19 July 19 19 19 19 19 19 19 19 19 19 19 19 19		***
Oreshort tons_	8, 210, 061	12, 606, 369	8, 818, 015	18, 090, 992
Pigdo	3, 476, 072	2 49, 706, 851	3, 712, 018	<sup>2</sup> 64, 037, 109
Limedo	234, 147	1, 359, 371	306, 836	1, 705, 558
Transactor of Comments of the	272	(1)	(1)	1, 100, 000
Manganiferous oredo	383	ζί		(7)
	A 4			
Mica: Scrapshort tons_	(1)	(1)	(1)	(1)
Sheet pounds	(1)	м	(1)	X
Sheet pounds Mineral waters gallons sold	(6)	(1) (6)	8	8
Ure (dry and siliceous) (gold and silver) short tong	900	$\vec{v}$	1.020	B
Sand and gravel do	1, 840, 945	936, 724	2, 428, 995	
Silver troy ounces	1,010,010	930, 724		1, 556, 457
Sand and gravel do Silver troy ounces. Stone short tons. Tin (metallic equivalent) do	2, 496, 480	3, 048, 043	3 004 740	0 747 071
Tin (metallic equivalent)		0, 040, 043	2, 804, 740	3, 745, 651
Miscellaneous 8	ารอสาสุดสาหารา	1, 114, 643	(1)	(1)
		1, 114, 043		8, 468, 526
Total value, eliminating duplications		64, 998, 018		82, 730, 210

1 Value included under "Miscellaneous."

2 Value not included in total value for State.

3 Exclusive of puzzolan, value for which is included under "Miscellaneous."

4 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

4 According to Bituminous Coal Division; value includes selling expenses.

No canyass.

Not valued as ore; value of recoverable metal content included under the metals.

Includes minerals indicated by "1" and "3" above.

### Mineral production of Alaska, 1940-41

	oj mada	1040 41		
Product	19	940	1941	
	Quantity	Value	Quantity	Value
Antimony ore (concentrates)short tonsdo	(1)	(1) (2)	(1)	(1)
Coal do	3 173, 970 110, 000	3 \$695,000 12,430	4 238, 960 144, 000	4 \$944, 588 16, 992
Lead short tons Mercury flasks (76 pounds)	755, 970 779 162	26, 458, 950 77, 900 28, 653	695, 467 662	24, 341, 345 75, 468
Ores (grude), etc.:  Coppershort tons  Dry and siliceous (gold and silver)do	4, 885, 023		144	g
Platinum metals (crude) troy ounces_ Sand and gravel short tons_	32, 300 515, 011	1, 093, 000 103, 217	4, 480, 364 (¹) 6 530, 997	(5) (1) 6 87, 116
Silvertroy ounces_ Stoneshort tons Tin (metallic equivalent)do	191, 679 (¹) 52	136, 305 (¹) 52, 000	191, 522	136, 193
Miscellaneous 7		66, 766	(1)	1, 207, 678
Total value, eliminating duplications		28, 724, 221		26, 809, 380

1 Value included under "Miscellaneous."
2 Figures not available.
3 According to the Alaskan Branch of the Geological Survey.
4 According to Bituminous Coal Division; value includes selling expenses.
5 Not valued as ore; value of recoverable metal content included under the metals.
6 "Government-and-contractor." Value of "Commercial" included under "Miscellaneous."
7 Includes minerals indicated by "!" and "6" above.

### Mineral production of Arizona, 1940-41

	19	1940		1941	
Product	Quantity	Value	Quantity	Value	
Antimony ore (concentrates)short tons_	(1)	(1) (3)	(2)	(2) (3)	
A manifesta orido			(3)	(8)	
A sheetos	1, 197	\$149, 290		(1)	
Bismuthpounds_	(8)	(3)	(3)	(3)	
Cleve			100		
Products (other than pottery and refractories)		4 306, 000		4 \$284,000	
Raw (sold by producers)short tons	(1)	(1)	(1)	(1)	
Cool	(1 5)	(i 5)	(1 5)	(1 5)	
Copper pounds Feldspar (crude) long tons	562, 338, 000	63, 544, 194	652, 634, 000	77, 010, 812	
Feldspar (crude)long tons	(1)	(1)	(1)	(1)	
	(1)	(1)	(1)	(1)	
		(6)		(6)	
Gold troy ounces	294, 807	10, 318, 245	315, 392	11, 038, 720	
Lead short tons	13, 266	1, 326, 600		1, 782, 732	
T.ima	67, 882	502, 998	58, 146	413, 095	
Manganese oredo	413	4, 940	(1)	(1)	
Monganiferous ore			(1)	(1)	
Manager (76 normal)	741)	130, 884	(1)	(1)	
Mice screp	(1)	(1) (1)	(1)	(1)	
Molybdonum DOHBOS	1 400.000	(1)	(1)	(1)	
Ores (crude), etc.: Coppershort tons_					
Coppershort tons_	20, 284, 826	$\binom{7}{7}$	24, 153, 483	(2)	
D d silicacona (gold and gilvor) do	U2X 44X	$\Omega$	975, 790	Ω	
Tead	8,810	$\Omega$	18, 432	(7)	
Lead-copperuo	12.3	(9)	663		
Zincdo			2, 143	$\Omega$	
Zinc-copper do do Zinc-lead do	79,044	(7)	80, 810	Ω	
Zinc-copperdo	271,000	(7)	260, 473	(7) 335, 474	
Sand and gravel	240,002	114, 500	702, 889		
Sand-lima brick EDOUSABUS OF DEICK.	(20)	(1 8) (1)	(3)	(8)	
Silica (quartz)short tons_	(1)		7, 498, 260	5, 332, 096	
Qilvor Irov ounces	7.075,215	5, 031, 264	7, 498, 260 455, 900	5, 332, 090 340, 872	
Stoneshort tons_	1, 149, 000	1, 043, 101	455, 900 (1 10)	(1 10)	
Sulfuric acid •dodo	(1 10)	(1 10)	1 5.7	1 (2.19)	
Tungsten ore (60-percent concentrates) do Vanadium pounds	349	471, 546		X	
Vanadiumpounds_	(1)	(1)	16, 493	2, 473, 950	
Zincshort tons_	15, 456	1, 947, 456 812, 684		2, 473, 930	
Miscellaneous 11		812, 084		2, 010, 918	
Total value, eliminating duplications				100, 472, 791	

1 Value included under "Miscellaneous."

Value included under "Miscenaneous."
 Less than 1 ton; value not recorded.
 Figures not available.
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 No canvass.
 Not related as one; value of recoverable metal content included under the metals.

No canvass.
Not valued as ore; value of recoverable metal content included under the metals.
1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.
From copper smelting.
Value not included in total value for State.
Includes minerals indicated by "1" above.

Mineral production of Arkansas, 1940-41

	19	40	41	
Product	Quantity	Value	Quantity	Value
Barite short tons Bauxite do Cement barrels	(1) 474, 077 (1)	\$2, 501, 393 (1)	(1) (1)	(1) (1) (1)
Clay: Products (other than pottery and refractories) Raw (sold by producers) Short tons Coal Gems and precious stones	24, 997 3 1, 453, 611	<sup>2</sup> 792, 780 13, 845 <sup>3</sup> 4, 879, 286 ( <sup>4</sup> )	15, 249 3 1, 574, 172	<sup>2</sup> \$1, 110, 000 14, 487 3 5, 882, 934 (4)
Gypsum (crude)         short tons           Lead         do           Lime         do           Manganese ore         do	55 (1) 6. 808	5, 500 (1) (1)	(1)	(1) 1, 254 (1) (1)
Manganiferous oredo		204, 992 (*)		(1) (4)

### Mineral production of Arkansas, 1940-41-Continued

Product	19	940	41	
Todate	Quantity	Value	Quantity	Value
Natural gas M cubic feet Natural gasoline and allied products: Natural gasoline gallons	14, 379, 000	\$2, 622, 000	19, 148, 000	\$2, 988, 000
Natural gasoline gallons do Oilstones and whetstones short tons	32, 096, 000	818, 000 (5)	28, 108, 000 6, 281, 000	1, 173, 000 57, 000
Ores (crude), etc.: Leaddo	(5)	(6)	100	(1) (1)
Zinc do Zinc-lead do Petroleum barrels	(5)	(6) (6)	1,800 1,100	(6) (9)
Sand and gravelshort tons_	25, 775, 000 2, 664, 178	21, 700, 000 1, 068, 701	26, 327, 000 3, 587, 906	24, 500, 000 1, 798, 307
Stoneshort tons	1, 222, 690 (¹)	1, 152, 328	<sup>7</sup> 1, 788, 470	<sup>7</sup> 1, 763, 196
Tripolidodododo	(¹) 440	(1) 55, 440 1, 664, 870	<sup>(1)</sup> 206	(i) 30, 900 7, 762, 248
Total value, eliminating duplications		37, 479, 135		47. 081, 326

### Mineral production of California, 1940-41

Product	19	140	19	41
	Quantity	Value	Quantity	Value
Andalusite short tons			(1)	<b>/</b> 1\
Antimony ore (concentrates) do	74	\$3, 700	(i)	K
Arsenious oxide do	(2)	(2), 100	2	2
Asbestos do			1 75	Ж
Asphalt (native)do	(1)	(1)	1 (1)	8
Barite do l	6	'n	719	X
Boron minerals do	243, 355	5, 643, 390	301, 282	\$6, 785, 662
Rromine novenda		(1)	(1)	40, 100, 002
Calcium chlorideshort tons	(1)	71	K	Ж
Cement barrels Chromite short tons	13, 813, 362	17, 296, 522	20, 186, 028	28, 019, 494
Chromiteshort tons	(1)	(1)	20, 100, 020	20,010, 20
Clav.	``'			()
Products (other than pottery and refractories)		3 8, 417, 000		8 8, 649, 000
Raw (sold by producers)short tons_	343, 526	926, 633	530, 140	1, 422, 511
Conner	12, 876, 000	1, 454, 988	7, 886, 000	930, 548
Diatomiteshort tons	(1)	1, 101, 100	1,000,000	(1)
Diatomite short tons. Feldspar (crude) long tons. Fuller's earth short tons. Gems and precious stones	2,711	18, 254	4, 464	22, 490
Fuller's earthshort tons	-,·,	10, 201	(1), 202	(1)
Gems and precious stones		(4)	(9,	- 33
troir oringe t	1, 455, 671	50, 948, 485	1, 408, 793	49, 307, 758
Gypsum (crude)short tons	259, 321	437, 504	381, 951	618, 685
lodinepounds	(1), 022	(1)	(1)	(1)
fron oreshort tons	1,200	X	59, 955	X
Kyanitedo	(1), 200	X	(1)	23
Leaddo	1,772	177, 200	3, 464	(4)
Limedo	112, 522	1, 031, 352	122, 375	394, 896
Lithium mineralsdo		(1)	122,010	1, 168, 767
Magnesite do do	(1)	X	132	(2)
Magnesium pounds	(9)	. (4)		(3)
Magnesium salts (natural)do	(1)		12, 810, 000	(1)
Manganese ore short tons	177	(1)	12, 510, 000	656, 297
Manganiferous oredo	97	1.2		(3)
Vergiry flocks (78 normal)	18, 629	(1) 3, 294, 911	$\mathbb{R}$	. (3)
Mercury flasks (76 pounds) Mica, scrap short tons	(1), 029	3, 294, 911	X	(1)
Mineral paints (zinc and lead pigments)do	(15)	(1)	(15)	(1)
Mineral watersgallons sold_	(%)	(.,)	(7,9)	(1.5)
Molybdenumpounds_	$\mathbb{R}$	22	(2)	<b>(*)</b>
Natural gas	251 050 000	00 000 000	074 007 055	(1)
descript Eas	201, 800, 000	90,006,000 (	374, 905, 000	96, 673, 000

<sup>1</sup> Value included under "Miscellaneous."
2 1940: Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
3 According to Bituminous Coal Division; value includes selling expenses.

No canyas.

Figures not available.

Not valued as ore; value of recoverable metal content included under the metals.

Exclusive of crushed marble, value for which is included under "Miscellaneous."

Includes minerals indicated by "" and "" above.

### Mineral production of California, 1940-41—Continued

생기 가게 되는 보면 없는 말이 맛있다며 다시다.		1940	40 1941		
Product	Quanti	ty Value	Quantity	Value	
Vatural gasoline and allied products:					
Natural gasoline	allons 587, 476,	000   \$27, 901, 000	577, 127, 000	\$24,067,000	
Tigunfied netroloum gases	do 1 (2)	1 (4)	82, 638, 000	<b>2, 082, 000</b>	
res (crude), etc.: Copper			000 000		
Copper shor	t tons 446,	392 (6)	292, 232	(6)	
Dry and siliceous (gold and silver)	_do 4, 214,	650 (6)	3, 968, 283	(6)	
Lead	_do '8,	199 J ( <sup>6</sup> )	18, 338	(6)	
Lead-copper	_do	199 (6) 11 (6)	2	(6) (6) (6)	
Zinc	_do		1, 330	(6)	
Zine Zine-lead Z	_do	181 (6)			
est	_do 4,	116 21, 110	3, 618	17, 898	
Pebbles for grinding	2do(1)	(1)	074	2,856	
Petroleum	arrels 223, 881,	000   216, 720, 000	230, 263, 000	239, 500, 000	
Platinum metals (crude)troy o	unces 1,	400 (1)	(1)	(1)	
Potassium saltsshor	t tons (1)	(1)	(1)	(1)	
Pumice	_do 32,	123   152, 885	77, 951		
vrites lön	g tons (1)	(1)	(1)	(1)	
alt (sodium chloride)shor	t tons 469,	354 2, 200, 640	484, 632	2, 290, 26	
and and gravel	_do 18, 913,	301   8, 988, 894	7 19, 617, 609	7 10, 988, 766	
and and sandstone (ground)	_do /5,	505 39,080	(1)	(1)	
and and gravel and and sandstone (ground) iiliea (quartz) troy c	_do (1)	(1)	2, 526	36, 72	
lilver troy o	unces 2, 359,	776 1, 678, 063	2, 154, 188	1, 531, 86	
late		(1)		53, 76	
at the terminal and and forted (nothing	ral) ` '				
shor	t tons 233,	590 2, 183, 110	218, 903	2, 224, 08	
shor strong minerals	_do 6, 340,		8 9, 139, 390	8 7, 535, 01	
strontium minerals	_do	287 4, 282	(1) 8, 803	(1)	
Sulfur lon	g tons (1)	(1) (1) (1 5)	8,803	139, 80	
Sulfuric acid 9 shor	t tons (1 5)	(1 5)	(1 8)	(1.5)	
strontium minerals sulfur lon sulfuric acid 9 shòr rale and ground soapstone Tripoli ripoli rungsten ore (60-percent concentrates)	_do  36,	282 476, 926	59, 203	811, 79	
Cripoli	do (¹)	(1)	(1)	(1)	
Cungsten ore (60-percent concentrates)	_do 2,	070 2, 561, 042	(1)	(1)	
line	_do	79 9, 954	440		
ingsten die (60-percent concentrates) Zinc Zircon	do		_ 30	54	
Miscellaneous 10		8, 155, 536	- 30	20, 707, 65	
	1	455 050 000		FOC 705 90	
Total value, eliminating duplications		455, 672, 038	1	506, 795, 39	

1 Value included under "Miscellaneous."

2 Figures not available.

3 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

4 No canvass.

5 Value not included in total value for State.

6 Not valued as ore; value of recoverable metal content included under the metals.

7 "Commercial.", Value of "Government-and-contractor" included under "Miscellaneous."

8 Exclusive of dimension unclassified stone, value for which is included under "Miscellaneous."

9 From roasting of high-sulfide gold and silver concentrates.

10 Includes minerals indicated by "1," "1," and "3" above.

#### Mineral production of Colorado, 1940-41

intineral production of Colorada, 20-40-42						
	19	1941				
Product	Quantity	Value	Quantity	Value		
Arsenious oxide short tons. Barite do Beryllium concentrates do Bismuth pounds Cement barrels	(2)	(1) (2) (3) (1) (2)	(1) (2) (1) (2)	(1) (2) (1) (2)		
Clay: Products (other than pottery and refractories) Raw (sold by producers) Short tons Coal. do Ocke	4 6, 588, 742	4 16, 644. 265 (2 5)	164, 444 4 6, 948, 532 703, 003			
Coke         do           Copper         pounds           Feldspar (crude)         long tons           Ferro-alloys         short tons           Fluorspar         do	11,032	123, 514 (2 5)	13, 496, 000 42, 326 (2 5) 15, 566	147, 64 (2 5)		
Fuller's earth do Gems and precious stones troy ounces Gold troy ounces Sypsum (crude) short tons Iron, pig do Gems and precious stones troy ounces short tons Iron, pig do Gems and Ge	367, 336 24, 641 (2 5)	12, 856, 760 36, 787 (2 5)	(2) (2 5)	(2) (2 5)		
Leaddo		1, 147, 600	12, 574	1, 433, 4		

### Mineral production of Colorado, 1940-41—Continued

	19	40	41	
Produet	Quantity	Value	Quantity	Value
Limeshort tonsdo	7, 944 251	\$82, 486	(2)	(2)
Manganierous oredo	3, 699	(2) (2)	(2)	(²)
	0,000	(-)		
Scrapdodo	(2)	(2)	(2)	(2)
Sneetpounds_			(2)	(2)
Mineral waters gallons sold	(6)	(6)	(6)	(8)
Molybdenum pounds Natural gas M cubic feet	18, 600, 897	(2)	(2)	(2)
Natural gas	2, 533, 000	573, 000	3, 256, 000	\$714,000
Natural gasoline gallons gallons	380,000	14,000	390, 000	18,000
Nickel short tons ores (crude), etc.:			(2)	(2)
Copperdodo	334, 312	<i>(</i> 100 − 10	207, 678	77
Dry and siliceous (gold and silver)do	1, 528, 737	8 1	1, 572, 763	9
Lead do	10, 199	m 1	7, 917	(i):
Lead-copperdo	1,037	<i>i</i> ή	4	m
Zincdodo	27	ďή	224	Ö
Zinc-leaddo	283, 453	(7)	434, 200	ďή
Peatdo	(2)	(2)	(2)	(2)
Petroleum barrels Pumice short tons	1, 626, 000	1, 480, 000	2, 150, 000	2, 300, 000
Pumiceshort tons	(3)	(2)		
Pyrites long tons	14, 473	34, 697	11,774	(2)
Salt short tons Sand and gravel do	(2) 1, 853, 359	(2)	(3)	(2)
Silver troy ounces	9, 710, 709	508, 403 6, 905, 393	8 809, 270 7, 301, 697	\$ 528, 116
Stone short tons	1, 089, 650	1, 067, 788	1, 104, 820	5, 192, 318 1, 073, 400
Sulfur ore long tons	89	1,000	49	550
Tungsten ore (60-percent concentrates) short tons	693	822, 988	(2)	
Vanadium pounds Vermiculite short tons	1, 897, 194	(2)	(2)	(2) (2)
Vermiculiteshort tons	(2)	(2)		
Zincdo	5,060	637, 560	15, 722	2, 358, 300
Miscellaneous 9		25, 105, 109		36, 897, 076
Total value, eliminating duplications		63, 188, 421		73, 960, 602

Figures not available.
 Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Value not included in total value for State.
 No express

- Value not included in other value for coale.
  No canvass.
  Not valued as ore; value of recoverable metal content included under the metals.
  "Commercial." Value of "Government-and-contractor" included under "Miscellaneous."
  Includes minerals indicated by "" and "" above.

#### Mineral production of Connecticut, 1940-41

Product	19	940	1941	
Froduct	Quantity	Value	Quantity	Value
Clay:	. Partie de			
Products (other than pottery and refractories)		1 \$1,007,612		1 \$1, 521, 000
Raw (sold by producers)short tons		(3)	(2)	(2)
Cokedo		(2 3) 128, 348	(2 3) 13, 693	(2 3)
ron ore short tons		120, 040	15, 095	92, 39
Lirhedo_	(2)	(3)	(2)	(2)
Mica:			, · ·	, ,
Scrapdo_	300	4,900	(2)	(2)
Sheet pounds		40, 316	(2)	(2)
Mineral watersgallons sold Peatshort tons		8	1 2	$\mathbb{C}^{2}$
and and graveldo	1, 646, 870	736, 317	2, 076, 977	941, 90
Stone dodo	1, 915, 990	1, 918, 132	\$ 2.244,900	5 2, 435, 84
Miscellaneous 6		3, 342, 258		3, 855, 97
			<u>-</u>	
Total value, eliminating duplications		3, 914, 177		5, 284, 95

<sup>1 1940:</sup> Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

2 Value included under "Miscellaneous."

3 Value not included in total value for State.

4 No canvass.

4 Exclusive of crushed granite, value for which is included under "Miscellaneous."

6 Includes minerals indicated by "" and "" above.

### Mineral production of Delaware, 1940-41

The short	194	40	1941	
Product	Quantity	Value	Quantity	Value
Clay: Products (other than pottery and refractories) Raw (sold by producers) Sand and gravel Stone do Miscellaneous	(2) 3 167, 138 114, 690	1 \$200, 000 (2) 3 91, 913 152, 313 13, 100	(2) 168, 359 109, 850	1 \$225,000 (2) 102,854 147,212 17,565
Total value, eliminating duplications	159/4/4 1 2	457, 326		492, 631

 <sup>1 1940:</sup> Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 2 Value included under "Miscellaneous."
 3 "Commercial." Value of "Government-and-contractor" included under "Miscellaneous."

#### Mineral production of the District of Columbia, 1940-41

	1940		1941	
Product	Quantity	Value	Quantity	Value
Clay products (other than pottery and refractories). Stone	(1)	(1 2) (1) \$640, 480		(1 2) \$700,000
Total value, eliminating duplications		640, 480		700, 000

### Mineral production of Florida, 1940-41

	19	940 1941		
Product	Quantity	Value	Quantity	Value
Cement barrels Clay:	(1)	(1)	(1)	(1)
Products (other than pottery and refractories)		2 \$153, 000		2 \$224,000
Raw (sold by producers)short tons_	(1)	(1)	(1)	(1)
Diatomitedo	(1)	(1)	(1)	(1)
Ferro-alloysdodo	(ì 3)	(ì 3)	(i 3)	(ì s)
Fuller's earthdo	(1)	(1)	(1)	(1)
Limedo	25, 038	227, 440	23, 265	216, 254
Mineral watersgallons sold	(4)	(4)	(4)	<b>(4)</b>
Peatshort tons.	(1)	(1)	(1)	(1)
Phosphate rocklong tons	2, 845, 012	7, 741, 177	3, 365, 572	10, 234, 031
Sand and gravelshort tons_	1, 162, 075	800, 085	1, 462, 276	949, 980
Stonedo	5 2, 880, 540	5 2, 750, 017	5 4, 065, 450	<sup>5</sup> 3, 852, 539
Titanium concentrates:				
Ilmenitedo	(1)	(1)	(1)	(1)
Rutuedo	(1)	(1)	(1)	(1)
Zircondo			144	4,608
Miscellaneous 6		3, 190, 127		3, 790, 719
Total value, eliminating duplications		14, 854, 206		19, 268, 779

¹ Value included under "Miscellaneous."
² 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 Value not included in total value for State.
 No canvass.

Exclusive of dimension unclassified stone in 1940 and of unclassified stone in 1941, value for which is included under "Miscellaneous."

6 Includes minerals indicated by "1" and "4" above.

### Mineral production of Georgia, 1940-41

	19	40	1941	
Product	Quantity	Value	Quantity	Value
Asbestos short tons Barite do Bauxite do Cement barrels Clay:  Products (other than pottery and refractories) Raw (sold by producers) short tons	(1) 92, 302 (1) (1) 595, 010	(1) \$464, 590 (1) (1) (2 2, 582, 000 4, 859, 826	(1) 104, 446 (1) (1) (1)	(1) \$553, 445 (1) (1) 2 2, 689, 000 6, 609, 605
Coaldo	\$ 42, 307 25, 200 (1)	<sup>3</sup> 100, 570 2, 848 (¹)	(1 3) (1)	(1 3) (1) (4)
Gems and precious stones	961	(4) 33, 635	(1) 311	(4) 10, 885 (1)
Shipped to furnaces, etc	112, 383 1, 057	182, 613 3, 144 (1)	290, 021 1, 926 (¹)	(1)
Lime do Manganese ore do Manganiferous or do Manganiferous ore do Manganiferous or d	13, 774 4, 001 11, 528	92, 281 68, 508 63, 761	12, 515 (1) (1)	(1) (1)
Scrap do Sheet pounds Mineral waters gallons sold	(1) (2)	() () ()	(1) (1) (9)	999
Ore (dry and siliceous) (gold and silver) short tons Sand and gravel	6, 963 490, 136 630	(4) (5) 231, 591 448 (1)	1, 641 615, 511 38	(5) 283, 148 27 (1)
Stone short tons Talc and ground soapstone do Miscellaneous 6.	2, 507, 600 20, 104	5, 034, 288 219, 959 2, 992, 273	2, 808, 790 28, 511	5, 809, 755 364, 560 4, 040, 023
Total value, eliminating duplications		16, 932, 335		21, 049, 261

### Mineral production of Idaho, 1940-41

	19	1940 1941		
Product	Quantity	Value	Quantity	Value
Antimony ore (concentrates) short tons.  Arsenious oxide do.  Bismuth pounds.  Cement barrels.  Clay:  Products (other than pottery and refractories) Raw (sold by producers) short tons.	(e) (e) (u)	\$18, 100 (2) (3) (1) 2 82, 000 (1)	() () ()	(1) (2) (2) (1) * \$122,000
Coal do do Copper pounds. Diatomite short tons. Garnet, abrasive do do Gems and precious stones	6, 698, 000 (1) (1)	(1 4) 756, 874 (1) (5)	7, 242, 000 (1) (1)	(1 4)- 854, 556 (1) (1) (5)
Gold troy ounces. Lead short tons. Lime do. Manganese ore do.	104, 834 (¹)	5, 126, 800 10, 483, 400 (¹)	149, 816 104, 914 120	5, 243, 560 11, 960, 196 2, 160
Manganiferous oredo  Mercuryflasks (76 pounds)  Ores (crude), etc.:	(1) 351	8	8	(4)
Copper short tons Dry and siliceous (gold and silver) do Lead do Lead-copper do Zinc. do Zinc-lead do Phosphate rock long tons.	4, 931 878, 993 164, 508 232 101 1, 507, 922 99, 088	(6) (6) (6) (9) 441, 598	7, 979 903, 510 212, 251 174 22, 551 1, 558, 215 97, 274	(6) (6) (6) (6) (6) (9) 444, 154

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Not valued as ore; value of recoverable metal content included under the metals.
 Includes minerals indicated by "1" above.

### Mineral production of Idaho, 1940-41—Continued

	19	40 ,	1941	
Product	Quantity	Value	Quantity	Value
Sand and gravel short tons Silver troy ounces Stone short tons Tungsten ore (60-percent concentrates) do Vanadium pounds	1, 943, 723 17, 552, 240 967, 900 260	\$657, 848 12, 481, 593 809, 797 (1)	2, 846, 752 16, 672, 410 767, 750	\$882, 867 11, 855, 936 644, 006
Zine. short tons Miscellaneous 7.	70, 601	8, 895, 726 1, 046, 184	79, 084	11, 862, 600 1, 801, 705
Total value, eliminating duplications	1 1204.14.1	40, 799, 920		45, 673, 740

<sup>&</sup>lt;sup>1</sup> Value included under "Miscellaneous."

### Mineral production of Illinois, 1940-41

	19	) <b>40</b>	19	11	
Product	Quantity	Value	Quantity	Value	
Cement	1 4, 937, 127  169, 938 2 50, 610, 430 3, 014, 840 (4-4) 104, 698 (9) 4, 093, 623 1, 508 161, 358 (4-5) (9) 8, 359, 000 21, 499, 000 (7) 50 41, 830 147, 647, 000 13, 021	1 \$7, 209, 431 2 7, 052, 000 4 19, 740 4 85, 584, 043 4 18, 217, 939 4 73, 882, 065 1 50, 800 1, 150, 113 (*) (*) (*) (*) (*) (*) (*) (*) (*) (*)	1 5, 958, 376  276, 016  276, 016  276, 016  3 54, 703, 284  3, 600, 878  (4 5)  133, 333  26, 676  5, 461, 459  (9)  10, 053, 000  54, 872, 000  38, 293, 000  72, 573  (1)  132, 393, 000  12, 026  13, 888, 985  131, 581  20, 340	<sup>3</sup> \$8, 660, 104 <sup>2</sup> 7, 977, 000 528, 136 <sup>3</sup> 98, 990, 565 <sup>4</sup> 25, 214, 769 (4 <sup>3</sup> ) 3, 047, 247 <sup>4</sup> 113, 558, 606 270, 864 1, 702, 129 (4 <sup>3</sup> )	
Zine do do Miscellaneous 12	4,818	155, 576 607, 068 3, 410, 794	13, 833 9, 198	200, 700 1, 379, 700 5, 986, 696	
Total value, eliminating duplications		277, 943, 011		320, 509, 559	

Figures not available.
 1940: Estimate by Bureau of Mines-based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.

No canyass.
 Not valued as ore; value of recoverable metal content included under the metals.
 Includes minerals indicated by "1" above.

Exclusive of natural cement, value for which is included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Value not included in total value for State.
 Value included under "Miscellaneous."
 No canyass

No canvass.

No canvass.
 Figures not available.
 Not valued as ore; value of recoverable metal content included under the metals.
 "Commercial." Value of "Government-and-contractor" included under "Miscellaneous."
 Exclusive of unclassified stone in 1940 and of sandstone in 1941, value for which is included under "Miscellaneous."
 IFrom zinc smelting.
 Includes minerals indicated by "1," "5," "9," and "10" above.

### Mineral production of Indiana, 1940-41

Product	19	<b>)40</b>	1941		
Product	Quantity	Value	Quantity	Value	
Cement barrels Clay:     Products (other than pottery and refractories) Raw (sold by producers) short tons Coal Coke do	89, 230	(1) 2 \$4, 265, 000 92, 712 3 28, 810, 864 4 37, 308, 469		(¹) <sup>2</sup> \$5, 967, 000 176, 367 <sup>3</sup> 38, 150, 201 <sup>4</sup> 48, 432, 824	
Ferro-alloys         do           Gold         troy ounces           Iron, pig         short tons           Lime         do           Marl, calcareous         do           Mineral paints (zinc and lead pigments)         do	5, 333, 915 84, 462		(1.4)	(1 4) 4 135, 655, 190 588, 879	
Mineral waters gallons sold  Natural gas	(5) 1, 137, 000 4, 978, 000 2, 734	(5)	(5) 1, 522, 000 7, 411, 000 (1)	(5) 906, 000	
Sand and gravel do Sand-lime brick thousands of brick. Stone short tons. Miscellaneous 8.	6, 265, 163 (1 6) 7 4, 498, 490	3, 306, 165 (1 e) 7 5, 822, 006 12, 636, 594	8, 897, 976 ( <sup>6</sup> ) 5, 257, 530	4, 560, 652 (6) 6, 742, 744 17, 083, 691	
Total value, eliminating duplications		58, 975, 110		80, 572, 397	

### Mineral production of Iowa, 1940-41

	19	940 1941		41
Product	Quantity	Value	Quantity	Value
Cement. barrels Clay: Products (other than pottery and refractories) Raw (sold by producers)short tons. Coal. do. Ferro-alloys. do. Gypsum (crude). do. Iron, pig. do. Mineral waters. gallons sold Peat. short tons. Sand and gravel. do. Miscellaneous 7.  Total value, eliminating duplications	4, 597, 781 10, 005 2 3, 231, 177 (3 4) 487, 379 (3 9) (2), 500 6 3, 464, 803 4, 013, 740	\$7, 641, 163  1 3, 649, 000 51, 267  2 8, 060, 587  (8 4) 587, 223 (8 4) (3) (3) (3) (3) (3) (4) (2) (3) (3) (3) (4) (2) (3) (3) (4) (2) (3) (4) (2) (3) (4) (4) (2) (4) (4) (5) (6) (6) (7) (8) (8) (8) (8) (9) (9) (9) (9) (9) (9) (9) (9) (9) (9	5, 328, 398 10, 022 2, 938, 626 (8 4) 630, 930 (8 4) (5) 6, 271, 702 5, 790, 920	\$8, 659, 014  1 3, 895, 000  2 8, 058, 700  2 8, 058, 700  (3 4)  736, 185  (3 4)  (3)  1, 728, 741  573  28, 872, 177

 <sup>1940:</sup> Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Value included under "Miscellaneous."
 Value not included in total value for State.
 Mocroposition

No canvass. "Commercial."

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 4 Value not included in total value for State.

No canvass.

1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.

Exclusive of unclassified stone, value for which is included under "Miscellaneous."

Includes minerals indicated by "" and "" above.

 <sup>&</sup>quot;Commercial." Value of "Government-and-contractor" included under "Miscellaneous."
 Includes minerals indicated by "" and "" above.

TOWNS OF THE MAKE THE

### Mineral production of Kansas, 1940-41

	19	<b>4</b> 0	1941		
Product	Quantity	Value	Quantity	Value	
Cement barrels Chats short tons	1 3, 441, 612 163, 180	1 \$5, 192, 160 25, 747	1 4, 734, 129 360, 951	<sup>1</sup> \$7, 136, 933 55, 447	
Clay: Products (other than pottery and refractories) Raw (sold by producers) Short tons	(3) 4 3, 578, 952	2 1, 035, 000 (3) 4 6, 717, 318	(3) 4 4, 007, 572	<sup>2</sup> 1, 121, 000 (3) <sup>4</sup> 7, 950, 431	
Coal	(3) 11,927 (3 5)	(3) 1, 192, 700 (3 5) (6)	(3)	(3) 1,657,332 (3 5) (6)	
Mineral waters gallons sold  Natural gas M cubic feet  Noting progline and allied products:		31, 931, 000	111, 121, 000	36, 552, 000	
Natural gasoline gallons June gallons do	64, 691, 000	1, 295, 000	72, 876, 000 12, 815, 000		
Ores (crude), etc.: Lead	2,014,096	(8) (8) (8)	1, 344, 123 2, 352, 124	(8)	
Petroleum         barrels           Pumice         short tons           Pyrites         long tons           Sait         short tons	66, 139, 000 39, 215	68, 700, 000 129, 959	83, 242, 000 23, 659 3, 902 781, 014	111, 835 (3)	
Sand and graveldodo	2, 264, 871	2, 710, 847 893, 962 3, 672, 644 7, 186, 032	2, 927, 921		
Zine do Miscellaneous •	57, 032	2, 760, 184		3, 852, 673	
Total value, eliminating duplications		130, 859, 896		171, 991, 68	

<sup>1</sup> Exclusive of natural cement, value for which is included under "Miscellaneous."

<sup>2</sup> 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete: 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

<sup>3</sup> Value included under "Miscellaneous."

<sup>4</sup> According to Bituminous Coal Division; value includes selling expenses.

<sup>5</sup> Value not included in total value for State.

<sup>6</sup> No cenyass

Value not included in total value for Seaso.
No canvass.
Figures not available.
Not valued as ore; value of recoverable metal content included under the metals.
Includes minerals indicated by "!" and "3" above.

### Mineral production of Kentucky, 1940-41

THE REPORT OF THE PROPERTY OF

	19	<b>140</b>	1941	
Product	Quantity	Value	Quantity	Value
Asphalt (native) short tons— Cement barrels—	(1)	(1) (1)	(1) (1)	(1)
Clay: Products (other than pottery and refractories) Raw (sold by producers)short tons	345, 023	2 \$1, 258, 000 1, 328, 644	503, 427	2 \$1, 690, 000 1, 978, 222
Cokedo	<sup>3</sup> 49, 140, 904	<sup>3</sup> 91, 153, 768	(1.4)	3116, 561, 332 (1 4)
Fluorspardododo	103, 939 290, 610	2, 043, 866 (1 4) 36, 000	142, 862 329, 125 282	2, 957, 982 (1 4) 32, 148
Lead         do           Lime         do           Mineral waters         gallons sold	(1)	(1) (5)	(5)	(5)
Natural gasoline and allied products:	53, 056, 000	22, 936, 000	69, 067, 000	28, 769, 000
Natural gasolinegallons_ Liquefied petroleum gasesdo	9, 539, 000	350, 000 (6)	10, 247, 000 25, 124, 000	475, 000 1, 055, 000
Ores (crude), etc.: Zincshort tons Zinc-leaddo	(6)	(7)	1, 455 14, 885	
Petroleumbarrels		5, 400, 000	4, 762, 000	6, 200, 000

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Divison; value includes selling expenses.
 Value not included in total value for State.
 No canvass.

No canvass.
 Figures not available.
 Not valued as ore; value of recoverable metal content included under the metals.

ではないとう こうしんしゃ おおとのいこいかいとう

## Mineral production of Kentucky, 1940-41-Continued

Product	19	940	1941		
	Quantity	Value	Quantity	Value	
Sand and gravel	1, 226, 325 4, 620, 750 1, 278	\$815, 688 4, 207, 875 161, 028 10, 740, 370	8 1, 654, 183 9 5, 779, 800 427	8 \$1, 124, 705 9 5, 177, 170 64, 050 14, 669, 799	
Total value, eliminating duplications		131, 974, 410		169, 009, 195	

 <sup>8 &</sup>quot;Commercial." Value of "Government-and-contractor" included under "Miscellaneous."
 9 Exclusive of sandstone, value for which is included under "Miscellaneous."
 10 Includes minerals indicated by "1," "8," and "9" above.

### Mineral production of Louisiana, 1940-41

Product	1	940 1941		
Cement herrole	Quantity (1)	Value	Quantity (1)	Value (1)
Clay: Products (other than pottery and refractories). Raw (sold by producers)	10, 189	2 \$540,000 96,314 (3) 63,577,000 2,552,000 (4) 107,500,000 2,804,406 1,381,044 (1) 8,688,064 2,014,484		2 \$874, 000 100, 339 (1) 71, 089, 000 6, 376, 000 3251, 492 2, 386, 000 132, 100, 000 3, 286, 902 (1) 8, 793, 904 3, 081, 212
Total value, eliminating duplications		189, 153, 312		228, 440, 044

### Mineral production of Maine, 1940-41

Product	1940		1941	
	Quantity	Value	Quantity	Value
Beryllium concentrates	(1)	(1) (1) 2 \$275,000	(1) (1)	(1)
Gems and precious stones long tons	18, 390	84, 796	22, 566	2 \$417,000 116,610
Mica:	(1)	6	(1)	8
Scrap	8	8	(1)	8
Sand and gravel short tons	8, 173 3, 836, 131	(3) 118, 897 878, 820	(3) 8, 527 3, 891, 656	(3) 178, 058 935, 902
Silica (quartz)do	160	538 286, 660	202	955, 902 722 442, 212
Stoneshort tons a	4 245, 580	4 1, 876, 198 854, 067	324, 060	1, 295, 180 1, 306, 764
Total value, eliminating duplications		4, 374, 976		4, 692, 448

Exclusive of unclassified stone, value for which is included under "Miscellaneous."
 Includes minerals indicated by "!" and "" above.

<sup>1</sup> Value included under "Miscellaneous."

1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

2 No canvass.

Figures not available.
Includes minerals indicated by "1" above.

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 No canvass.

### Mineral production of Maryland, 1940-41

Product	1940		1941	
	Quantity	Value	Quantity	Value
Asbestos	(1)	(1) (1) 2 \$1, 856, 000	(1)	(1)
Raw (sold by producers) short tons.  Coal do Coke do Feldspar (crude) long tons.  Iron, pig short tons.  Lime do Mineral waters gallons sold.  Potassium salts short tons.  Sand and gravel do Silica (quartz) do Slate.	49, 036 8 1, 503, 433 1, 682, 701 2, 350, 773 63, 745 (8) (1) 3, 426, 525 (1)	114, 531 * 3, 171, 243 (1 4) (1)	57, 489  8 1, 700, 574  1, 752, 538 (1) 2, 372, 932 65, 624 (5) (1) 5, 167, 445 (1)	2 \$2,042,000 149,744 3 4,088,426 (1 4) (1) (1 4) 431,200 (5) (1) 4,446,850
Stone short tons Tale and ground soapstone do Miscellaneous 6	1, 109, 960 (¹)	1, 395, 373 (¹) 46, 596, 893	1, 604, 430 15, 628	2, 218, 478 105, 363 60, 911, 136
Total value, eliminating duplications		12, 605, 171		17, 291, 523

### Mineral production of Massachusetts, 1940-41

		1940		1941	
Product		Quantity	Value	Quantity	Value
Clay: Products (other than pottery and ref Baw (sold by producers) Coke. Feldspar (crude) Iron, pig. Lime. Manganiferous ore. Mineral waters Pest. Sand and gravel. Sand and sandstone (ground) Sand-lime brick. Silica (quartz) Stone. Miscellaneous <sup>6</sup> Total value, eliminating duplication	short tons. long tons. short tons. do. do. llons sold. short tons. do. do. short tons. do. do. do. do. do. do. do. do. do. do	(3) 1, 130, 311 (13) 108, 797 2, 128 (1) 703 3, 563, 760 1, 425 (2) 7, 786 2, 176, 340	1 \$976, 895 (2) (2) (3) 965, 333 (3) (4) 965, 333 (4) 1, 681, 222 6, 240 (2) 1, 708 9, 436, 083 7, 573, 122	(2) 1, 161, 732 (2) (4 3) 106, 336 (2) (4) (9) 5, 351, 002 1, 352 (5) 850 2, 602, 120	1 \$1,022,000 (2) (3) (2) (2) (3) (1) 1,007,773 (2) 2,674,557 (5),327 (5) 5,525 4,547,808 15,178,812

<sup>1 1940:</sup> Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

2 Value included under "Miscellaneous."

3 Value not included in total value for State.

4 No canvass.

5 1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.

6 Includes minerals indicated by "2" above.

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Value not included in total value for State.
 No canvass.
 Includes minerals indicated by "" above.

The state of the s

Mineral production of Michigan, 1940-41

		40	1941	
Product	Quantity	Value	Quantity	Value
Brominepounds_	14, 173, 936	\$2,878,900	15, 899, 731	\$3, 906, 486
Calcium chlorideshort tons_	84, 918	900, 801	148, 918	1, 236, 783
Cementbarrels	8, 519, 416	11, 389, 191	9, 819, 218	13, 333, 850
Clay:				
Products (other than pottery and refractories)		1 2, 377, 000		1 2, 925, 000
Raw (sold by producers)short tons_	(2)	(2)	(2)	(2)
Coal do	* 410, 169	3 1, 592, 051	3 310, 775	<sup>8</sup> 1, 312, 777
Cokedo	2, 872, 026	4 15, 445, 452	2, 863, 563	4 18, 213, 048
Copperpounds_	90, 396, 000	10, 214, 748	92, 880, 000	10, 959, 840
Gems and precious stonesshort tonsshort tons _		(5)		(5)
Gypsum (crude)short tons_	746, 982	1, 017, 126	805, 861	1,090,309
Iron:				
Oredo	15, 402, 206	40, 474, 951	17, 025, 813	43, 765, 164
Pigdo		4 18, 472, 588	1, 360, 139	4 21, 384, 383
Limedo	41, 814	308, 926	55, 447	388, 104
wagnesiumpounds_	12, 823, 633	3, 462, 380	(2)	(3)
Magnesium salts (natural):				
Carbonatedo	(2)	(2)	1,922,000	181, 255
Carbonate do Chloride do	(2)	(2)	(2)	(2)
Sulfate do	(2)	(2)	(2)	(2)
Manganiferous oreshort tonsdo	20, 851	(2) (2) (2) (2) (5)		
Marl, calcareousdo	(2)	(2)	66, 854	35, 684
Mineral waters gallons sold	(2) (5)	(8)	(5)	(5)
Natural gas M cubic feet	12, 648, 000	8, 339, 000	13, 916, 000	8, 722, 000
Natural gasoline gallons	3, 919, 000	162,000	5, 670, 000	261,000
Natural gasoline gallons Ores (crude), etc.: Copper short tons	4, 438, 219	(6)	4, 282, 448	(6)
Peatdo	5, 326	32,750	11, 340	75, 500
Peatdobarrels_	19, 753, 000	20, 150, 000	16, 359, 000	21, 900, 000
Salt short tons	2, 863, 035	7, 479, 905	3, 620, 649	10, 975, 872
Salt short tons Sand and gravel do Sand-lime brick thousands of brick	13, 650, 528	4, 978, 006	15, 606, 215	6, 190, 336
Sand-lime brick thousands of brick	7 14, 564	7 170, 678	(7)	(7)
Silvertroy ounces_	88, 657	63, 045	60, 796	43, 233
Stone short tons	13, 527, 170	6, 891, 433	15, 161, 820	
Miscellaneous 8		1, 891, 690		6, 780, 873
Total value, eliminating duplications		124, 774, 581		142, 433, 673

<sup>1 1940:</sup> Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

2 Value included under "Miscellaneous."

3 According to Bituminous Coal Division; value includes selling expenses.

4 Value not included in total value for State.

5 No canvass.

6 Not valued es any value of

Not valued as ore; value of recoverable metal content included under the metals.
7 1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.
8 Includes minerals indicated by "2" above.

Mineral production of Minnesota, 1940-41

	1940		1941	
Product	Quantity	Value	Quantity	Value
Cementbarrels_ Clay:	(1)	(1)	(1)	(1)
Products (other than pottery and refractories)		2 \$988, 116		2 \$1, 119, 000
Raw (sold by producers) short tons Coke do Gordon do Gor	(1) 524, 360	³ 3, 662, 908	(1) 685, 873 (1 3)	<sup>3</sup> 5, 082, 787
Flint lining for tube millsdododo	(1)	(1)	(1)	(9)
Iron: Oreshort tons_ Pigdo	53, 652, 633 282, 728	118, 947, 968	70, 419, 878 369, 549	167, 781, 967
Limedo	(1)	(1)	(3)	) jg'
Manganiferous ore do	1, 171, 939 (¹)	2, 894, 388 (1)	21, 387	11, 664
Mineral waters gallons sold peat short tons	1,984	19, 980	8	(4)
Pebbles for grindingdo	(1)	(1)	b b	8
Sand and graveldodo Sand-lime brickthousands of brick	8, 729, 205	1, 924, 716 (1 5)	13, 517, 069 (5)	2, 705, 534 (5)
Stone short tons Short tons	1, 119, 230	1, 987, 822 7, 083, 749	1, 002, 190	1, 811, 805 13, 944, 941
Total value, eliminating duplications		128, 571, 690		178, 790, 274

<sup>&</sup>lt;sup>1</sup> Value included under "Miscellaneous."
<sup>2</sup> 1940: Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
<sup>3</sup> Value not included in total value for State.
<sup>4</sup> No cenuses

Value not included in total value for Season.
 No canvass.
 No canvass.
 1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.
 Includes minerals indicated by "1" above.

8

San San Call

Contract of the second

### Mineral production of Mississippi, 1940-41

	1940		1941	
Product	Quantity	Value	Quantity	Value
Clay: Products (other than pottery and refractories) Raw (sold by producers) Iron ore	(2) 56 (3) 56 6, 365, 000 4, 400, 000 2, 319, 073 5 210	1 \$787,000 (2) 38 (3) 1,637,000 3,750,000 724,777 5 410 340,422	92, 479 57 (3) 4, 268, 000 15, 327, 000 4 2, 192, 829 500	1 \$915,000 420,322 101 (3) 1,084,000 14,000,000 41,018,504 5 750 312,049
Total value, eliminating duplications.		7, 239, 647		17, 750, 726

 <sup>1940:</sup> Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 2 Value included under "Miscellaneous."

6 Includes minerals indicated by "2," "4," and "5" above.

#### Mineral production of Missouri, 1940-41

Product	19	1940		1941	
Froduct	Quantity	Value	Quantity	Value	
Asphalt (native)	3, 587 172, 052 607, 062	(1) \$1, 216, 069 7, 616, 247 238, 266 22, 064, 000 1, 400, 932 26, 320, 770 (14) 154, 810 123, 234 111, 177 17, 205, 200 3, 184, 293	(1) 212,718 6,516,345 2,182,372 805,813 3,145,288 (14) 2,800,000 15,019 5,671 165,909 736,200 (1) (14)	(1) \$1,337,756 10,272,509 458,696 2 3,032,000 1,798,342 3 7,013,745 3 330,400 35,543 36,649 18,913,626 4,106,468 (1)	
Natural gas. M cubic feet. Ores (crude), etc.: Lead. short tons. Zinc do. Zinc do. Zinc-lead do. Petroleum barrels. Pyrites long tons. Sand and gravel short tons. Sand and sandstone (ground) do. Sand-lime brick thousands of brick. Silver troy ounces. Stone short tons. Tripoli do. Trungsten ore (60-percent concentrates) do. Miscellaneous §	201, 055 418, 795 44, 000 29, 325 4, 057, 571 (1) (17) 260, 314 6, 085, 790 (1)	166,000 (9) (9) (9) 34,000 74,088 2,311,221 (17) 185,112 6,176,867 (1) 1,600,578 1,876,041		100,000 (e) (e) 41,000 3,220,086 (1) (7) 261,467 7,048,207 (1) (1) 3,289,800 2,364,610	

No canvass.
"Commercial."

<sup>4 &</sup>quot;Commercial." Value of "Government-and-contractor" included under "Miscellaneous."

5 Exclusive of limestone in 1940 and of sandstone in 1941, value for which is included under "Miscel-

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Value not included in total value for State.
 No canvass.
 No canvass.

Not valued as ore; value of recoverable metal content included under the metals.
 1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.
 Includes minerals indicated by "1" above.

### Mineral production of Montana, 1940-41

	1940		1941	
Product	Quantity	Value	Quantity	Value
Antimony ore (concentrates) short tons Arsenious oxide do	(1) (1)	\$3, 000 (1) (1)	(1) (1)	(1) (1)
Bismuthpounds Cementbarrels	(2) (1)	(2) (1)	(2) (1)	(2) (1)
Clay: Products (other than pottery and refractories). Raw (sold by producers)short tons	(1)	³ 155, 000	<del>(1)</del>	* \$231,00
Coal: Bituminousdo	4 2, 818, 936	(1) 4 4, 075, 528	4 3, 194, 931	(1) 4 4, 725, 39
Lignitedo Copperpounds Gems and precious stones	48, 264 252, 782, 000	86,000 28,564,366	58, 793 256, 072, 000	105, 00 30, 216, 49
Gems and precious stones		(5) 9, 541, 070	246, 475	8, 626, 62
Gold troy ounces_ Graphite, crystalline pounds Gypsum (crude) short tons_ Lead do	(¹) 23, 036	(¹) 2, 303, 600	(1) (1) 21, 259	(1) (1) 2, 423, 52
Limedo	18, 797	77, 658	(1)	(1)
Manganese ore do do Manganiferous ore do gallons sold gallons sold	(5)	(1) (5)	(1)	(1)
Natural gas M cubic feet Natural gasoline and allied products:	26, 231, 000	7, 132, 000	28, 499, 000	7, 597, 00
Natural gasoline gallons Liquefied petroleum gases do	2, 603, 000 (²)	162, 000 (²)	2, 517, 000 1, 449, 000	177,00 81,00
Ores (crude), etc.:  Coppershort tons_ Dry and siliceous (gold and silver)do	3, 287, 803 1, 028, 523	(6) (6)	3, 791, 202 940, 067	(6) (6)
Lead-copperdo	29, 454 71	6	33, 029 4	(6) (6)
Zine do Zine-lead do Petroleum barrels	174, 181 579, 209 6, 728, 000	(6) (6) <b>6,</b> 660, 000	182, 745 695, 202 7, 526, 000	(°) (6) 8, 000, 00
Phosphate rocklong tons Platinum metals (crude)troy ounces	64, 239	184, 844 (¹)	105, 108	318, 58 (1)
Pyriteslong tonsshort tons	(1) 4, 978, 353	(1) 1,953,009	(1) 4,706,685	1, 871, 91
Silver troy ounces Stone short tons Falc do	12, 361, 050 829, 600	8, 790, 080 813, 286	12, 386, 925 455, 680	8, 808, 48 336, 63
Fin (metallic equivalent)pounds Fungsten ore (60-percent concentrates) _short tons	<sup>(1)</sup> 50	(1) (1)		(i)
Vermiculitedododo	(1) 52, 587	(1) 6, 625, 962	(1) 60, 710	9, 106, 50
Miscellaneous 7  Total value, eliminating duplications		2, 360, 470 79, 487, 873		3, 958, 30 86, 583, 46

### Mineral production of Nebraska, 1940-41

Product	1940		1941	
	Quantity	Value	Quantity	Value
Cementbarrels_	(1)	(1)	(1)	(1)
Products (other than pottery and refractories) Raw (sold by producers)short tons Mineral watersgallons sold	10, 417	<sup>2</sup> \$412,000 5,781 (3)	11, 969 (3)	2 \$659,000 6,048 (3)
Petroleum barrels Pumice short tons	276,000 (1)	220,000 (1)	1, 898, 000 7, 512	1, 600, 000 54, 513
Sand and graveldo Stonedodo	3,051,706 832,890	1, 072, 935 906, 563 2, 074, 867	3, 176, 701 4 328, 690	1, 273, 066 4 660, 573 2, 245, 870
Total value, eliminating duplications		4, 692, 146		6, 499, 070

<sup>1</sup> Value included under "Miscellaneous."
2 Figures not available.
3 1940: Estimate by Bureau of Mines based of figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
4 According to Bituminous Coal Division; value includes selling expenses.
4 Not avaisate as a contraction of the Census.

4 Not avaisate as a contraction of the Census.

5 Not avaisate as a contraction of the Census.

Not valued as ore; value of recoverable metal content included under the metals. Includes minerals indicated by "1" above.

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

No canvass.
 Exclusive of dimension limestone, value for which is included under "Miscellaneous."
 Includes minerals indicated by "" and "" above.

# Mineral production of Nevada, 1940-41

	19	40	19	41
Product	Quantity	Value	Quantity	Value
Andalusiteshort tons_	(1)	(1)		
Antimony ore (concentrates)do	361	\$22,100	(1)	(1)
Baritedo	(1)		(1) (1) (2)	[ K
Bismuth pounds.	(2)	(1) (2)	2	2
Clay:	· · · ·		1	(-)
Products (other than pottery and refractories)  Raw (sold by producers)  short tons	(1)	(1 3) (1)	(1)	(1 3)
Cobaltpounds_	] · · · · · · · · · · · · · · · · · · ·		410	N
Copperdo	156, 908, 000	17, 730, 604	157, 822, 000	\$18, 622, 996
Diatomiteshort tons_		(1)		410, 022, 990
Dumortieritedo	(1)	Ж	(1)	K
Fluorspardo	5, 803	$\mathbb{R}$	8, 967	1 13
Fuller's earthdo	(1)	$\mathbb{R}^{2}$	(1)	1 13
Gems and precious stones	(-)	$\mathcal{L}$	()	1 12
Goldtroy ounces_	383, 933	13, 437, 655	366, 403	12, 824, 105
Graphite, amorphous short tons	(1)	10, 401, 000		12, 824, 100
Gypsum (crude)do	250, 632	618, 050	(1)	774 004
Iron ore dodo	200, 002	010,000	284, 795	754, 294
Leaddodo		749, 900	241	645
Limedo	(1), 499	749, 900	9, 623	1,097,022
Magnesitedo		$\mathcal{M}$		
Magnesium oxide (hydrated) (brucite)do	XX	\ <u>\</u>	1 53	
Manganese oredodo	235	);;	(3)	(1)
Manganiferous oredo		<b>X</b>	$\mathbb{R}$	$\Omega$
Marl, calcareous dodo	(1)	SX.	1 2	1 93
Mercury flasks (76 pounds)	5,924	1,047,778	$\mathbb{R}$	1 12
Mineral waters gallons sold		1,047,778	1 12	1 52
Ores (crude), etc.:	(4)	(3)	(*)	(*)
Coppershort tons_	6, 158, 388	(5)	6, 850, 444	<b>(</b> 10)
Dry and siliceous (gold and silver) do	2,044,000	(5)	1, 783, 923	\ <u>\</u>
Leaddo	7,080	(5) (5)	26, 838	(5) (5)
Lead-copperdo	1,000	8	20,000	(9)
Zincdo	1,968	(5) (5)	1, 488	
Zinc-leaddo	126, 814	(5)	136, 942	(8)
Sand and graveldo	1, 803, 924	543, 036	2, 170, 145	894, 721
Silvertroy ounces_	5, 175, 928	3, 680, 660	5, 830, 238	4, 145, 947
Stone short tons	171, 670	189, 143	183, 170	226, 827
Sulfur ore long tone	41	403	100,170	503
Sulfur orelong tons	(1)	(1)	13, 178	126, 433
Tungsten ore (60-percent concentrates) do	1 796 1	X	(1)	(1) (1)
Zinedo	11, 833	1, 490, 958	15, 129	2, 269, 350
Miscellaneous 6	11,000	3, 060, 242	10,129	5, 378, 167
		J, 000, 242		0, 010, 101
Total value, eliminating duplications		42, 570, 529		46, 341, 010
		, 0.0, 020		20, 012, 010

1 Value included under "Miscellaneous."
2 Figures not available.
3 1940: Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
4 No canvass.
5 Not valued as ore; value of recoverable metal content included under the metals.
6 Includes minerals indicated by "1" above.

### Mineral production of New Hampshire, 1940-41

Product	19	40	1941	
Flodaci	Quantity	Value	Quantity	Value
Beryllium concentrates short tons			(1)	(1)
Clay products (other than pottery and refractories) Feldspar (crude) Llong tons Gems and precious stones	38, 589	2 \$204, 228 149, 031 (3)	52, 219	<sup>2</sup> \$389, 000 200, 569 ( <sup>3</sup> )
Mica: Scrap	(!)	Ω.	(1)	g)
Mineral waters gallons sold	(3) 143	(3) (3) 2, 116	(1)	(3)
Peat. short tons. Sand and gravel do Scythestones do	2, 132, 525 (1)	266, 338 (1)	1,894,074	1, 773 336, 538
Silica (quartz) do do do	4 51, 250	4 409, 616	(1) 4 167, 270	(i) 4 373, 157
Miscellaneous 5		34, 008		81, 469
Total value, eliminating duplications		1, 065, 337		1, 382, 506

1 Value included under "Miscellaneous."
2 1940: Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
3 No canvass.
4 Exclusive of basalt, value for which is included under "Miscellaneous."
4 Includes minerals indicated by "1" and "4" above.

The state of the s

### Mineral production of New Jersey, 1940-41

Product	19	40	1941		
Trouble 1	Quantity	Value	Quantity	Value	
Cementbarrels_	(1)	(1)	(1)	(1)	
Clay:					
Products (other than pottery and refractories)		<sup>2</sup> \$6, 489, 000		2 \$7, 052, 000	
Raw (sold by producers)short tons	95, 186	529, 914			
Cokedo	1, 016, 481	(1 8)	1, 031, 569	(1.8)	
Ferro-alloysdodo	(1 3)	(1.8)	(1 3)	(1.8)	
ron oredo	777, 278	3, 328, 467	746, 536	3, 437, 082	
do	28, 854	206, 326	(1)	(1)	
Manganiferous residuumdodo	172, 990	(1)	(1)	(9)	
Marl, greensanddo	6, 697	389, 888	11, 120	619, 664	
Mineral paints (zinc and lead pigments)do			(1 3)	(1 8)	
Mineral watersgallons sold	(4)	(4)	(4)	(4)	
Ore (zinc)short tons	556, 031	(5)	585, 463	(5)	
Peatdo	10,056			55, 969	
land and graval do	4, 918, 350	3, 846, 902	5, 964, 869	4, 897, 039	
Sand and sandstone (ground)dodo	(1)	(1)	(1)	(1)	
and-lime brick thousands of brick	(1 6)	(ì 6)	(6)	(6)	
Silica (quartz)short tons	(1)	(1)	(1)	(1)	
Stonedo	2, 705, 170	2, 888, 339	3, 206, 050	3, 782, 036	
Talcdo	(1)	(1)	<u></u>		
Zine 7do	91, 406	13, 121, 911	93, 781	14, 855, 073	
Miscellaneous 8		9, 814, 738		11, 230, 738	
Total value, eliminating duplications		33, 653, 732		39, 074, 518	

Mineral production of New Mexico, 1940-41

	19	40	1941	
Product	Quantity	Value	Quantity	Value
Arsenious oxide short tons	(1)	(1) (1)	(1)	(1)
Bismuthpounds	(1)	(1)	(1)	(1)
Clay:	4.1	9 000 000		2 \$185,000
Products (other than pottery and refractories)	11, 378	2 \$98, 000 18, 322	13, 458	22, 934
Raw (sold by producers)short tons	<sup>3</sup> 1, 110, 615	3 3, 304, 046		3 3, 788, 488
Coal do do popper pounds	139, 696, 000	15, 785, 648	146, 956, 000	17, 340, 808
Copper	139, 090, 000	10, 100, 040	140, 330, 000	11, 320, 303
Diatomiteshort tons	1 12	$\mathcal{X}$	· X	X
Fluorspardo Fuller's earthdo	(A)	· X	$\mathbf{X}$	$\sim$
	(3)	<b>X</b>	(3)	X
Gems and precious stones	35, 943	1, 258, 005	27, 845	974, 575
Gold troy ounces Lead short tons	3, 822	382, 200	4, 668	532, 152
Limedo	(4)	(4)	(4)	(4)
Manganese oredo	50	. X	(5)	(9
Manganiferous oredodo		(4)	(4)	(4)
	41, 200	, (9	(7)	(-)
Mica: Scrapdodo	(4)	(4)	(4)	(4)
Sheetpounds_	( <del>1</del> )	<b>X</b>	X	<b>X</b>
Mineral waters gallons sold	(5)	<b>&gt;</b> 5	\dis	\s\ \s
Molyhdonum nounds	1, 897, 063	<b>1</b>	<b>16</b>	<b>X</b>
Molybdenum pounds. Natural gas	63, 990, 000	10, 317, 000	64, 655, 000	11, 339, 000
Natural gasoline and allied products:	00, 000, 000	10, 011, 000	02, 000, 000	11,000,000
Natural gasoline gallons gallons	55, 713, 000	879, 000	69, 115, 000	2,049,000
Liquefied petroleum gasesdo	(1)	(1)	11, 885, 000	228,000
		` ' '	,000,000	,
Ores (crude), etc.: Coppershort tons_ Dry and siliceous (gold and silver)do	6, 606, 471	(6)	6, 975, 682	(6)
Dry and siliceous (gold and silver) do	127, 014	(6)	108, 017	. (6)
Leaddo	1,901	(6)	2, 261	(6)
Zincdo	123, 126	(6)	148, 359	(6)
Zinc-leaddo	231, 391	(6)	295, 907	(6)
Petroleumbarrels	39, 129, 000	32, 500, 000	39, 569, 000	<b>37, 200, 0</b> 00
Potassium salts short tons	(4)	(4)	7 433, 677	14, 084, 716
Pumicedo	(4)	(4)	<b>(4)</b>	(4)
Salt dodo	13, 915	41, 573	16, 641	51, 514
Sand and graveldodo	8 2, 364, 939	8 1, 141, 380	8 1, 948, 587	8 1, 269, 813
Silvertroy ounces	1, 407, 839	1,001,130	1, 328, 317	944, 581
Stoneshort tons	362, 020	223, 680	118, 180	111, 709

See footnotes at end of table.

<sup>&</sup>lt;sup>1</sup> Value included under "Miscellaneous."
<sup>2</sup> 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
<sup>3</sup> Value not included in total value for State.

<sup>Value not included in total value for State.
No canvass.
Not valued as ore; value of recoverable metal content included under the metal.
1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.
Value reported for zinc in New Jersey is estimated smelting value of fécoverable zinc content of ore after freight, haulage, smelting, and manufacturing charges are added.
Includes minerals indicated by "1" above.</sup> 

# Mineral production of New Mexico, 1940-41-Continued

Product	1940		1941	
Product	Quantity	Value	Quantity	Value
Tin (metallic equivalent)short tons_ Tungsten ore (60-percent concentrates) do Zincdo Miscellaneous •	(4) 98 30, 313	(4) (4) \$3, 819, 438 10, 200, 301	(4) (4) 37, 862	(4) (4) \$5, 679, 300 2, 047, 496
Total value, eliminating duplications		80, 969, 723		97, 849, 086

Pagures not available.
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete;
 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Value included under "Miscellaneous."

Value included under interceptations.
No canyass.
Not valued as ore; value of recoverable metal content included under the metals.
Equivalent as K<sub>2</sub>O.
"Government-and-contractor." Value of "Commercial" included under "Miscellaneous."
Includes minerals indicated by "4" and "8" above.

Mineral production of New York, 1940-41

The second secon

Cement	9, 589 1, 038 1, 038 1 1, 040 1, 44 1, 046 1, 046 1, 046 1, 046	Value 2, 700, 000 11, 687, 089 5, 820, 000 (2) 9, 519, 871 (2) 9, 349	(2)	Value (1 2) 3 \$16, 073, 726
Cement	1,038   4   4   6   6   6   6   6   6   6   6	11, 687, 089 5, 820, 000 (2) 9, 519, 871 (2)	11, 446, 292	3 \$16, 073, 72
Clay:	1,038	11, 687, 089 5, 820, 000 (2) 9, 519, 871 (2)	(2)	3 \$16, 073, 72
Products (other than pottery and refractories).         Raw (sold by producers)         5,00           Coke	0, 403 1, 046 9, 303	5, 820, 000 (2) 9, 519, 871 (2)	(2)	
Raw (sold by producers)	) 0, 403   1 29 1, 046   9, 303   1 30	9, 519, 871 (2)	(2)	•
Haw (sold by producers)   Short tons   Coke   Go   Go   Go   Go   Go   Go   Go   G	) 0, 403   1 29 1, 046   9, 303   1 30	9, 519, 871 (2)	(2)	4 8, 111, 000
Coke         do         5,08           Diatomite         do         6           Emery         do         6           Feldspar (crude)         long tons.         2           Ferro-alloys         short tons.         2           Garnet, abrasive         do         (3           Gems and precious stones         (1         (2           Graphite:         Artificial         pounds.         (1           Crystalline         do         6           Gypsum (crude)         short tons.         79           Iron:         Ore-         Sold to furnaces         do         (3           Sold for paint         do         (3         3         20           Lead         do         3         20	) 1, 046 ) 9, 303   1 30	(2)		-0,111,000
Distomite	) 1, 046 ) 9, 303   1 30	(2)		1 20 000 000
Emery         do           Feldspar (crude)         long tons           Ferro-alloys         short tons           Garnet, abrasive         do           Gems and precious stones         (a           Graphite:         do           Artificial         pounds           Crystalline         do           Gypsum (crude)         short tons           Iron:         To           Sold to furnaces         do           Sold for paint         do           Lead         do           Lime         do           Marl, calcareous         do           Mica:         scrap           Scrap         do           Millstones         (a           Mineral waters         gallons sold           Natural gas         M cubic feet           Natural gasoline         gallons           Ores (crude), etc.:         2           Zinc         short tons           2inc-lead         do           11         11           2peat         do           12inc-lead         do           12inc-lead         do           12inc-lead         do           12	1, 046 ) 9, 303   1 30		5, 116, 308	1 32, 808, 93
Feldspar (crude)         long tons.           Ferro-alloys         short tons.           Garnet, abrasive         do.           Graphite:         do.           Artificial         pounds.           Crystalline         do.           Gypsum (crude)         short tons.           Iron:         To           Sold to furnaces         do.         (a           Sold for paint         do.         (a           Fig.         do.         3, 20           Lead         do.         5           Lime         do.         5           Mica:         Scrap.         do.           Sheet         pounds.         (a           Millstones         gallons sold.         (b           Millstones         gallons         (c           Mineral waters         gallons         (c           Natural gasoline         gallons         (c           Ores (crude), etc.:         11         12, 18           Natural gasoline         do.         31           Ores (crude), etc.:         11         2, 10           Zinc-lead         do.         13           Peat         do.         13	) 9, 303   1 30		(2)	(3)
Ferro-alloys	9, 303   1 30		4, 876	42, 48
Garnet, abrasive   Gems and precious stones   Graphite:   Artificial   pounds   Crystalline   do   Gypsum (crude)   short tons   Ton:   Sold to furnaces   do   Garden   Gar		(2)	(2)	(2)
Gems and precious stones Graphite:     Artificial		0, 719, 756	(ì 2)	(ì 2)
Graphite:	<i>)</i>	(2)	(2)	(2)
Artificial pounds C1 Crystalline do do Gypsum (crude) short tons from:  Ore Sold to furnaces do (2 Sold for paint do (3 Sold for paint do (4 Sold for paint do (5 Sold for paint do (6 Lead do (6 Lime do (7 Lead		(5)		(2) (5)
Crystalline				` ` `
Crystalline	)	(12)	(1 2)	(1 2)
Gypsum (crude)	<b>'</b>	` '	(2)	(2)
Iron: Ore	8, 229	1, 037, 181	1,080,320	1, 500, 30
Ore—Sold to furnaces         do         (2           Sold for paint         do         (3           Plg         do         3, 20           Lead         do         5           Lime         do         5           Marl, calcareous         do         5           Mica:         do         6           Scrap         do         (2           Sheet         pounds         (3           Millstones         Millstones sold         (6           Millstones         M cubic feet         12, 18           Natural gasoline         gallons         0           Ores (crude), etc.:         Zinc         short tons         31           Zinc-lead         do         1           Peat         do         1           Pertroleum         barrels         4,99           Pyrites         long tons         6           Salt         short tons         2,11           Sand and gravel         do         13,22           Sand and lime brick         thousands of brick           Silica (quartz)         short tons         3	,,	1,001,101	1,000,020	1, 000, 00
Sold for paint				1
Sold for paint	.	(2)	/s\	(0)
Pig.       do.       3, 20         Lead       do.       5         Lime       do.       5         Marl, calcareous       do.       5         Mica:       do.       6         Sheet       pounds       (2         Millstones       gallons sold       (8         Mineral waters       gallons sold       (8         Natural gas.       M cubic feet       12, 18         Natural gasoline       gallons       0         Ores (crude), etc.:       Zinc       short tons       31         Zinc-lead       do       1         Peat       do       1       4,99         Pyrites       long tons       6       6         Salt       short tons       2,11       3         Sand and gravel       do       13,22       2         Sand (quartz)       short tons       3       12         Silica (quartz)       short tons       3       3	( )		(2)	(2)
Lead		(2)	9, 243	56, 900
Lime         .do         5           Marl, calcareous         .do            Mica:              Scrap               Sheet   <		4, 150, 107	3, 724, 989	1 66, 718, 244
Marl, calcareous       .do         Mica:       .do         Scrap       .do         Sheet       .pounds         Millstones       .do         Mineral waters       .gallons soid         Natural gas       .M cubic feet       .12, 18         Natural gasoline       .gallons       .0         Ores (crude), etc.:       .short tons       .11         Zinc-       .short tons       .11         Peat       .do       .31         Petroleum       .barrels       .4, 99         Pyrites       .long tons       .6         Salt       .short tons       .2, 11         Sand and gravel       .do       .713, 22         Sand-lime brick       .thousands of brick         Silica (quartz)       .short tons       .3         Silver       troy ounces       .3	1, 973	197, 300	2, 100	239, 400
Mica: Scrap.	4, 364	408, 645	62, 339	463, 230
Scrap			(2)	(2)
Sheet	1	1		
Sheet		(2)	(2)	(2)
Milistones       gallons sold.       (4         Mineral waters       gallons sold.       (4         Natural gas.       M cubic feet.       12, 18         Natural gasoline       gallons.       1         Ores (crude), etc.:       1       1         Zinc.       short tons.       31         Peat.       do.       1         Petroleum       barrels.       4, 99         Pyrites.       long tons.       6         Salt.       short tons.       2, 11         Sand and gravel       do.       713, 22         Sand-lime brick       thousands of brick.       3         Silica (quartz)       short tons.       (2         Silver       troy ounces.       3	,	(2)	(2) (2)	(2) (2)
Mineral waters     gallons sold.       Natural gas.     M cubic feet.       Natural gasoline.     gallons.       Ores (crude), etc.:     11       Zinc.     short tons.       2 inc-lead.     do.       Peat.     do.       Pyrites.     long tons.       Salt.     short tons.       2, 11       Sand and gravel.     do.       And-lime brick.     thousands of brick.       Silica (quartz).     short tons.       Silver.     troy ounces.		(2)		3, 558
Natural gas         M cubic feet.         12, 18           Natural gasoline.         gallons         1           Ores (crude), etc.:         short tons.         1           Zinc.         short tons.         31           Peat.         do.         4,99           Petroleum         barrels.         4,99           Pyrites.         long tons.         6           Salt.         short tons.         2,11           Sand and gravel.         do.         713,22           Sand-lime brick         thousands of brick.         (2           Silica (quartz)         short tons.         (2           Silver         troy ownes         3		(5)	(5)	(5)
Natural gasoline       gallons         Ores (grude), etc.:       11         Zinc       short tons       31         Peat       do       1         Petroleum       barrels       4,99         Pyrites       long tons       6         Salt       short tons       2,11         Sand and gravel       do       713,22         Sand-lime brick       thousands of brick         Silica (quartz)       short tons       (2         Silver       troy ounces       3	7 000   S	8, 246, 000	10, 456, 000	7, 853, 000
Ores (crude), etc.:       11         Zinc.       do	7,000	1,000		
Zinc	,000	1,000	17,000	1,000
Zinc-lead	. 171	أدم	151 000	
Peat.         do         1           Petroleum         barrels         4,99           Pyrites         long tons         6           Salt         short tons         2,11           Sand and gravel         do         713,22           Sand-lime brick         thousands of brick         (2           Silver         troy ounces         3	6, 171	(6)	151, 808	(6)
Petroleum         barrels         4, 99           Pyrites         long tons         6           Salt         short tons         2, 11           Sand and gravel         do         713, 22           Sand-lime brick         thousands of brick           Silica (quartz)         short tons           Silver         troy ounces           3	6, 048	(6)	336, 271	(6)
Pyrites	9, 352	148, 433	13, 905	105, 120
Salt       short tons       2, 11         Sand and gravel       do       713, 22         Sand-lime brick       thousands of brick       (2         Silica (quartz)       short tons       (2         Silver       troy onnes       3		1, 600, 000	5, 185, 000	13, 300, 000
Sand and gravel do 7 13, 22 Sand-lime brick thousands of brick (2 Silica (quartz) short tons (2 Silver troy ounces 3	4, 498	233, 816	63, 958	(2)
sand-ime brick thousands of brick (2 Silica (quartz) short tons (7 Silver troy ounces 3		3, 523, 775	2, 719, 586	7, 416, 734
sand-ime brick thousands of brick (2 Silica (quartz) short tons (7 Silver troy ounces 3		7, 639, 668		7 10, 096, 875
Silvertrov ounces   3		(28)	(8)	(8)
Silvertrov ounces   3	5, 133 77	(2)	(2)	(2)
Cloto	5, 133 77 8)	25, 401	37, 734	26, 833
JIAU	5, 133 77 8)		01, 104	685, 145
	5, 133 77 8)	470 052	10 400 740	
	5, 133 7 7 5, 720	479, 053	10, 406, 740	10, 806, 450
dine de la companya d	5, 720 2, 120	), 398, 401	153, 560	1, 917, 732
Miscallanaous I	5, 133 7 7 5, 720 10 2, 120 10 3, 611 1	), 398, 401 l, 402, 524	-00, 000 1	5, 766, 900
Miscellaneous 9	5, 133 7 7 5, 720 10 2, 120 10 3, 611 1	0, 398, 401 1, 402, 524 1, 496, 436	38, 446	
Total value, eliminating duplications	5, 133 7 7 5, 720 10 3, 611 1 5, 686 4 6	0, 398, 401 1, 402, 524 1, 496, 436	38, 446	78, 083, 628
arbitonionioni	5, 133 7 7 5, 720 2, 120 10 8, 611 1 5, 686 4 6	0, 398, 401 1, 402, 524 4, 496, 436 3, 080, 854	38, 446	78, 083, 628 91, 582, 704

Value not included in total value for State.
 Value included under "Miscellaneous."
 Exclusive of natural cement, value for which is included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

Not canvass.
Not valued as ore; value of recoverable metal content included under the metals.
"Commercial." Value of "Government-and-contractor" included under "Miscellaneous."
1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.
Includes minerals indicated by "2," "4," and "7" above.

### Mineral production of North Carolina, 1940-41

	19	940	194	11
Product	Quantity	Value	Quantity	Value ,
Aluminum short tons Asbestos do Bromine pounds	29, 441 (2) (3)	1\$10, 746, 000 (2) (2)	(1 2) (2) (2)	(1 2) (2) (2)
Clay: Products (other than pottery and refractories) Raw (sold by producers)short tons	14, 620	3 4, 629, 000 202, 678	(2) (2)	* \$5, 356, 000 (2) (2)
Copper pounds Feldspar (crude) long tons Flint lining for tube mills short tons Carnet abresive	(2) 79, 312 (2)	426, 784	100, 016 (2) (2)	552, 386 (2) (2)
Garnet, abrasive	1,943	(2)	3, 244 (2) (2)	(4) 113, 540
Lithium minerals do do Manganese ore do	(2)	(2)	(2) (2) (2) (2) (2) (2)	(?) (?) (?) (?)
Manganiferous ore do Marl, calcareous do Marl, calcareous do Mica:		173, 327		
Scrap do Sheet pounds Millstones gallons sold	1,002,646	218, 154 (2) (4)	(2)	(2) (2) (3)
Olivineshort tons_ Ores (crude):	2,500	15,000	4, 828 19, 402	24, 401 (5)
Dry and siliceous (gold and silver) do Pebbles for grinding do Sand and gravel do Sand and sandstone (ground) do	7, 927 (2) 3, 213, 855	(5) (5) (2) 1, 439, 457	14, 344 6, 099 4, 473, 297	(5) 102, 895 2, 345, 165
Silver troy ounces Stone short tons	(2) 6, 480 3, 031, 300	4,850,277	(2) 7, 439 3, 820, 200	(2) 5, 290 4, 806, 623
Talc and pyrophyllite do Vermiculite do Miscellaneous 6 do Miscellaneous 8 do Miscellaneous 9 do Miscellaneo	39, 206	298, 382 8, 070 8, 778, 990	64, 783	567, 921 (2) 17, 882, 755
Total value, eliminating duplications		21, 112, 732		18, 915, 461

### Mineral production of North Dakota, 1940-41

	19	40 19		941	
Product	Quantity	Value	Quantity	Value	
Clay: Products (other than pottery and refractories) Raw (sold by producers) Short tons.  do. Mineral waters Sand and gravel Stone Miscellaneous Total value, eliminating duplications.	2, 218, 434 (3) 3, 202, 167 (1)	(1 *) (1) \$2,587,000 (3) 298,646 (1) 101,705 2,987,351	2, 308, 888 3, 47, 000 2, 636, 039 18, 590	(1 2) (1) \$2, 937, 000 (3) 16, 000 238, 864 19, 713 116, 050 3, 327, 627	

<sup>&</sup>lt;sup>1</sup> Value not included in total value for State.

<sup>2</sup> Value included under "Miscellaneous."

<sup>3</sup> 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

<sup>4</sup> No canvass.

<sup>8</sup> Not valued as ore; value of recoverable metal content included under the metals.

<sup>6</sup> Includes minerals indicated by "2" above.

Value included under "Miscellaneous."
 1940: Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 No canvass.
 Includes minerals indicated by "1" above,

# Mineral production of Ohio, 1940-41

	19	<b>140</b>	1941		
Product	Quantity	Value	Quantity	Value	
Brominepounds Calcium chlorideshort tons	- (2)	(1) (1)	(1)	8	
Cementbarreis	2 6, 841, 129	2 \$9, 202, 414	2 8, 021, 857	2\$10, 657, 677	
Clay: Products (other than pottery and refractories)	514, 257	\$ 24, 711, 000 1, 058, 016	741, 655	3 27, 556, 000 1, 711, 068	
Raw (sold by producers) short tons Coal do	4 22, 771, 552	4 39, 039, 016	4 29, 318, 843	4 58, 473, 076	
Coke do	189, 499	<sup>5</sup> 38, 568, 313 <sup>5</sup> 8, 793, 122	9, 284, 194	5 48, 491, 596 (1 5) 426, 929	
		278, 274 (¹)	(1)	(1)	
Grindstones do do dypsum (crude) do liron, pig do Lime do Marl, calcareous do	.   10, 275, 696 .   1, 284, 877			12, 482, 100	
		(1) (1 5) (6)	(1)	(1 5)	
Mineral watersgallons sold	40, 639, 000	20,850,000	41, 858, 000		
Natural gasoline gallons Peat short tons Petroleum barrels	8, 062, 000 2, 531	24, 087	8, 217, 000 1, 495	11, 34	
Petroleum barrels Salt short tons	3, 159, 000 2, 080, 133	4, 100, 000 2, 781, 599	3, 510, 000 2, 510, 096		
		7, 182, 453	12, 473, 145		
Sand and sandstone (ground)do Seythestones, whetstones, etcdo	(i)	(i)	Ö	(i)	
Stilica (quartz) do Stone do	1 ' 11, 910, 020	7 10, 234, 221	7 13, 842, 870	7 12, 469, 49	
Strontium minerals do Sulfuric acid 8 do Miscellaneous 9 do Miscellane	(1 5)	(i i)	(1 5)	(1 5) 15, 215, 92	
Total value, eliminating duplications					

¹ Value included under "Miscellaneous."
² Exclusive of natural cement, value for which is included under "Miscellaneous."
² Exclusive of natural cement, value for which is included under "Miscellaneous."
² 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
² According to Bituminous Coal Division; value includes selling expenses.
² Value not included in total value for State.
² No canvass.
² Exclusive of unclassified stone, value for which is included under "Miscellaneous."
² From zinc-roasting operation.
² Includes minerals indicated by "1," "2," and "?" above.

# Mineral production of Oklahoma, 1940-41

	19	) <del>4</del> 0	1941	
Product	Quantity	Value	Quantity	Value
Asphalt (native)short tons	(1)	(1)	(1)	(1)
Cement Darrels	(1)		2, 748, 168	(1) \$383, 797
Chatssnort tons	2, 152, 877	\$308,726	2, 748, 108	<b>\$300, 19</b>
Clay: Products (other than pottery and refractories)		2 532, 000		2 838, 00
Raw (sold by producers)short tons	(1)	(1)	(1)	(1)
Cool do	3 1, 645, 981	8 4, 021, 760	3 1, 771, 108	3 4, 700, 10
Coal do do Gypsum (crude) do do	176, 166	227, 534	258, 258	344, 48
Iron ore	( (-)	(1)	233	(1)
Lead	21, 240		25, 021	2, 852, 39
Lime do	(1)	(1)	Ω	1 (2)
Manganese oredo				1 🐰
Manganise ore do Mineral waters gallons sold Natural gas M cubic feet			4	
Mineral waters gallons sold	257, 626, 000	31, 603, 000	234, 054, 000	29, 821, 00
Natural gas	201, 020, 000	31,003,000	201,001,000	20,021,00
Natural gasoline and allied products:  Natural gasolinegallons	399, 369, 000	8, 926, 000	362, 247, 000	16,084,00
Liquefied petroleum gasesdo	(8)	(5)	91, 136, 000	2,076,00
Ores (crude), etc.:		1		
Lead short ton	3		15, 589	(6)
Zinc do	5,813,405	(6)	6, 430, 723	(6)
Zinc-lead	5, 436, 995	(6)	7, 437, 677	174 900 00
Petroleum Darrel	3 156, 164, 000	162, 500, 000	154, 702, 000	174, 800, 00
Pumice Short ton	S  (*)	(1)	10, 743	(1) 42, 73
Saltdo_	1 020 425			
Sand and graveldo	1,030,435	284,010	1, 513, 988	627

See footnotes at end of table.

A CONTRACT OF THE PROPERTY OF

## Mineral production of Oklahoma, 1940-41—Continued

Deadnot	19	1940 194		11
Product	Quantity	Value	Quantity	Value
Stone	1, 311, 640 (1 8) (1) 162, 935	\$1, 217, 525 (1 8) (1) 20, 529, 810 3, 710, 833	1, 876, 570 (1 8) (1) 166, 602	\$1, 945, 753 (1 8) (1) 24, 990, 300 4, 695, 858
Total value, eliminating duplications		235, 535, 062		263, 763, 923

### Mineral production of Oregon, 1940-41

	19	40	19-	41
Product	Quantity	Value	Quantity	Value
Antimony ore (concentrates)	176, 000 (1) 113, 402 35	(1) 3, 969, 070 3, 500 (1) 1, 599, 436	(1) (2) (1) (1) (1) (1) (1) (1) (1) (1) (1) (2) (1) (3) (4) (1) (5) (6) (7) (7) (8) (8) (9) (1) (1) (1) (1) (1) (1) (1) (1) (1) (1	(1) (2) (1) (1) (1) (1) (2) (1) (1) (1) (1) (1) (1) (1) (1) (1) (1
Mineral waters	146 105, 318 5 (1) 8 1, 622, 921 1, 600 219, 112 9 2, 757, 820	(°) (°) (°) (°) (°) (°) (°) (°) (°) (°)	97, 531 (¹) 677 3, 968, 395 (¹) 276, 158 2, 836, 390	(6) (7) (7) (8, 544 2, 159, 470 (1) 196, 379 2, 436, 783 4, 763, 948 12, 830, 176

<sup>1</sup> Value included under "Miscellaneous."

<sup>1</sup> Value included under "Miscellaneous."
2 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
3 According to Bituminous Coal Division; value includes selling expenses.
4 No canvass.
5 Figures not available.
6 Not valued as ore; value of recoverable metal content included under the metals.
7 From zinc smelting.
8 Value not included in total value for State.
9 Includes minerals indicated by "1" above.

Yaiue included under "Miscellaneous."
 Figures not available.
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Value not included in total value for State.

<sup>7</sup> Not valued as ore; value of recoverable metal content included under the metals.

8 "Commercial." Value of "Government-and-contractor" included under "Miscellaneous."

8 Exclusive of sandstone, value for which is included under "Miscellaneous."

10 Includes minerals indicated by "1," "8," and "9" above.

## Mineral production of Pennsylvania, 1940-41

	19	940	19	41
Product	Quantity	Value	Quantity	Value
Asbestos short tons Cement barrels Clay:	27, 499, 786	<sup>2</sup> \$38, 350, 998	2 32, 868, 220	² \$45, 383, 76
Products (other than pottery and refractories) Raw (sold by producers)short tons	899, 173	* 11, 031, 000 2, 189, 509	1, 234, 367	<sup>8</sup> 12, 550, 00 3, 045, 68
Anthracite do Bituminous do Cobalt pounds	4 116, 602, 999	205, 490, 000 4 237, 333, 374	56, 368, 267 4 130, 239, 683	4 296, 912, 29
Cokeshort tons_	17, 412, 024	5 69, 599, 076	(1)	(1)
Copper 6 pounds Feldspar (crude) long tons. Ferro-alloys short tons Gems and precious stones troy ounces	512, 174	5 56 002 912	1	(1) (1 s) (7)
Ore—		A STATE OF		
Sold to furnaces short tons Sold for paint do Pig do	14, 571, 517	(1) (1) 5 282, 666, 561	10, 020, 000	(1) 15, 63 344, 298, 43
Limedo Mica, scrapdo Mineral paints (zinc and lead pigments)do	- (1.5)	(1.5)	1, 003, 039 (1) (1 5)	7, 263, 77 (1) (1 5)
Mineral waters gallons sold Natural gas M cubic feet. Natural gasoline and allied products:	90, 725, 000	41, 733, 000	92, 819, 000	42, 974, 00
Natural gasolinegallons Liquefied petroleum gasesdo Peatshort tons	_ 8.310	(8) 23, 540	15, 440, 000 571, 000 5, 440	42, 00 12, 60
Petroleum barrels. Pyrites long tons. Sand and gravel short tons.	- (1) 8, 431, 656	(1)	16, 750, 000 (1) 10, 515, 940	(1)
and and sandstone (ground) do thousands of brick	- (1)	(1) (1 9) (1)	(1) (9) (1)	(1) (9) (1)
Silver 6troy ounces_	13, 064	2 609 801	15, 016	(1)
oapstone short tons. tone do ulfuric acid (60° Baumé) 11 do Tripoli (rottenstone) do	299, 751	\$ 2,739,724	10 23, 506, 540 351, 722	10 25, 013, 4 5 2, 986, 1
Miscellaneous 12		15, 290, 396		115, 331, 9

The second secon

½ Value included under "Miscellaneous."

Value included under "Miscellaneous."
 Exclusive of natural cement, value for which is included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Value not included in total value for State.
 Copper, gold, and silver were recovered from magnetite-pyrite-chalcopyrite ore, which is included as iron ore produced. Bureau of Mines not at liberty to publish figures.
 No canvass.

of the Census; 1941: No canvass.

8 Figures not available.

10 1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.

10 Exclusive of dimension basalt in 1940 and of marble in 1941, value for which is included under "Miscellaneous."

11 From gine smalling.

Miscentaneous. 11 From zinc smelting. 12 Includes minerals indicated by "1," "2," and "10" above.

#### Mineral production of Rhode Island, 1940-41

Product	19	40	1941	
Froduct	Quantity	Value	Quantity	Value
Clay products (other than pottery and refractories) Coke	(1 3) (1) (4) 515, 129 5201, 380	(1 2) (1 3) (1) (4) \$333, 612 \$511, 620 1, 960, 840 994, 997	(1 3) (1) (4) 649, 289 212, 580	(1 2) (1 3) (1) (4) \$459, 22 493, 71 2, 142, 41 1, 133, 40

1 Value included under "Miscellaneous."

2 1940: Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

3 Value not included in total value for State.

Value not included in 1921
 4 No canvass.
 5 Exclusive of dimension basalt, value for which is included under "Miscellaneous."
 6 Includes minerals indicated by "" and "" above.

さいまというないというない。

# Mineral production of South Carolina, 1940-41

Product	19	940	1941	
Troube	Quantity	Value	Quantity	Value
Bariteshort tons_	(1)	(1)	(1)	(1)
Products (other than pottery and refractories) Raw (sold by producers)short tons	152, 529	2 \$1, 688, 000 1, 306, 438	181, 322	2 \$1, 860, 000 1, 604, 047
Copperpounds_ Gems and precious stones Goldtroy ounces_	13,076	(3) 457, 660	1,000	(3) 542, 780
Mica: Scrapshort tons	(1)	(1)	(1)	(1)
Sheetpounds Mineral watersgallons sold Ore (dry and siliceous) (gold and silver)short tons	(1) (3)	(1) (3)	(1)	(1)
Sand and graveldosilvertroy ounces	126, 607 515, 247 8, 047	260, 857 5, 722	135, 288 1, 125, 725 6, 525	611, 469 4, 640
Stone short tons Short tons	<sup>5</sup> 1, 233, 610	<sup>5</sup> 1, 570, 689 16, 141	2, 055, 090	2, 574, 797 38, 652
Total value, eliminating duplications		5, 305, 597		7, 236, 503

# Mineral production of South Dakota, 1940-41

	<del>, , , , , , , , , , , , , , , , , , , </del>	<del></del>		
Product		940	41	
	Quantity	Value	Quantity	Value
Beryllium concentrates short tons—Cement barrels—Clay:	(1)	\$2,064 (1)	(1)	\$7, 067 (¹)
Products (other than pottery and refractories) Raw (sold by producers) Short tons Coal Copper Dounds Feldspar (crude) long tons	40, 481 66, 085		57, 139 70, 825	
Gentle and precious stones troy ounces. Gold troy ounces short tons	586, 662	157, 323 (8) 20, 533, 170	59, 015 600, 637	170, 723 (3) 21, 022, 295
Iron ore sold for paint.	717	(1) 700	2, 408 (1) 3, 636	(1)
Mica: Scrapdo	2, 240	32, 074 12, 509	(2)	(2)
Mineral waters gallons sold Natural gas M cubic feet Ores (crude), etc.: Dry and siliceous (gold and silver) short tons. Lead	1, 667, 289	(4) (4)	7, 000 1, 711, 744	2, 000 (4)
Sand and gravel	2, 910, 331 (1 5) 175, 514	(4) 524, 842 (1 s) 124, 810	2, 627, 059 ( <sup>5</sup> ) 170, 771	559, 766 (5) • 121, 437
Stone	255, 600	878, 866 1, 710 893, 687	6 401, 550 (1) (1)	6 1, 189, 564 (1) (1) (1) 842, 311
Total value, eliminating duplications		23, 528, 825		24, 501, 696

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 No canvass.
 Not valued as ore; value of recoverable metal content included under the metals.
 Exclusive of unclassified stone, value for which is included under "Miscellaneous."
 Includes minerals indicated by "1" and "" above.

<sup>1</sup> Value included under "Miscellaneous."
2 1940: Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
3 No canvass.
4 Not valued as ore; value of recoverable metal content included under the metals.
5 1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.
6 Exclusive of unclassified stone, value for which is included under "Miscellaneous."
7 Includes minerals indicated by "1" and "4" above.

# Mineral production of Tennessee, 1940-41

	1940		1941	
Product	Quantity	Value	Quantity	Value
Aluminum short tons	82, 256	1 \$30,023, 000	(1 2)	(1 2)
Baritedodo	70, 767	503, 204	104, 511	\$779, 565
Cement barrels	3, 766, 807	5, 655, 635	5, 623, 800	8, 520, 284
Clay:	1.0			
Products (other than pottery and refractories)		3 1, 869, 000		\$ 2, 401, 000
Raw (sold by producers)short tons_	89, 582	491, 271	159, 304	832, 50
Coaldodo	4 6, 008, 456	4 12, 024, 742	4 7, 045, 271	4 16, 454, 539
Okedo	99, 705	1 618, 746	150, 393	1 1, 118, 72
Copperpounds_	(2)	(2)	(2)	· (2)
Ferro-alloys short tons	38, 900	1 3, 041, 405	(ì ź)	(ì ź)
Flint lining for tube mills			(2)	(3)
Fuller's earthdo	(2)	(2)	(3)	(²)
Foldtroy ounces	173	6,055	227	7, 94
ron:				
Ore—		40		
Sold to furnacesshort tons_	(2)	(2)		
Sold for paintdo	(1 2)			
Pigdo		(1 2)	(1 2)	(1 2),
Sinter from copper sulfide oredo	(2)	(2)	(2)	(2)
Leaddo	573	57, 300	23	2, 622
Limedo	192, 133	1, 050, 199	239, 528	1, 354, 642
Manganese oredo	8, 308	120, 736	(2) (2)	(2) (2)
Manganiferous oredodo	2,606	(2)	\X	(8)
Mineral waters gallons sold Natural gas M eubic feet	(5) 9,000	3,000	10,000	5,000
Natural gas	9,000	3,000	10,000	5,000
Ores (crude), etc.: Coppershort tons_	705, 574	(6)	732, 114	76\
Leaddo	8,709	8	469	8
Zincdo	1, 206, 786	6	1, 300, 347	\display
Zinc-lead do do	1, 200, 780	(6)	1,000,011	(6)
Petroleum barrels	24,000	23,000	12,000	15,000
Phosphate rocklong tons	(2)	(2)	(2)	(2)
Pyritesdo	2	2	2	}₂⟨
Sand and gravel short tons	3, 104, 382	2, 255, 287	4, 811, 686	2, 829, 83
Silica (quartz)do	(2)	(2)	(2)	(2)
Silvertroy ounces_	38, 610	27, 456	39, 161	27.84
Stoneshort tons_	5, 604, 170	6, 674, 710	7, 896, 970	9, 157, 67
Sulfuric acid 7do	(1 2)	(1 2)	(1 2)	(1 2)
Zincdo	34, 796	4, 384, 296	36, 170	5, 425, 500
Miscellaneous 8	01,.00	8, 832, 008		51, 854, 34
MAIDOUINIA CONTRACTOR		0,002,000		
Total value, eliminating duplications	r	42, 683, 407	1	56, 301, 59

Value not included in total value for State.
 Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Not anvass.
 Not valued as ore; value of recoverable metal content included under the metals.
 From copper smelting.
 Includes minerals indicated by "2" above.

Mineral production of Texas, 1940-41

	19	40	194	1941	
Product	Quantity	Value	Quantity	Value	
Asphalt (nstive) short tons. Barite do Bromine pounds. Cement barrels	158, 220 100 7, 383, 600	\$306, 120 450 12, 198, 800	294, 170 (1) (1) (1) 9, 842, 260	\$550, 206 (1) (1) 16, 362, 293	
Clay: Products (other than pottery and refractories) Raw (sold by producers) Short tons Coal:	92, 719	2 3, 173, 000 407, 873	137, 937	2 4, 121, 000 331, 873	
Bituminous         do	\$ 14, 137 606, 418 60, 000	<sup>3</sup> 48, 278 637, 000 6, 780	3 15, 482 337, 326 12, 000	\$ 52,730 284,000 1,416	
Fint lining for tube mills short tons Fluorspar do Fuller's earth do Gems and precious stones	34, 039	277, 229 (4)	(1) (1) 77, 033	(1) (1) 713, 085 (4)	

See footnotes at end of table.

## Mineral production of Texas, 1940-41-Continued

	19	<b>)40</b>	941	
Product	Quantity	Value	Quantity	Value
Fold troy ounces	312	\$10,920	306	\$10.71
ypsum (crude)short tons_	328, 261	368, 882	446, 419	467.08
Heliumcubic feet_		\$ 85, 061		(1 5)
			(1.5)	(1)
ron oreshort tons_	(1)	20, 500	186	21, 20
_eaddo	205	20, 500		
_imedo	64, 274	543, 130	77, 783	632,09
Magnesitedodo	(1)	(1)	8,900	44,50
Magnesiumpounds_			(1)	Ω
Magnesium sulfate (natural) do Mercury flasks (76 pounds) Mineral waters gallons sold Vatural gas M cubic feet	.[ (¹)	(1) (1)	(1)	(4)
Mercuryflasks (76 pounds)	.[ (1)	(1)	(1)	(1)
Mineral watersgallons sold	. (4)	(4)	(4)	(4)
Natural gas	1,063,538,000	151, 580, 000	1,086,312,000	162, 344, 00
Natural gasoline and allied products:				
Natural gasoline and cycle productsgallons	932, 040, 000	20, 322, 000	1,180,221,000	44, 066, 00
Liquefied netroleum goses do	(6)	(8)	378, 598, 000	4, 416, 00
Ores (crude), etc.: Copper short tons Dry and siliceous (gold and silver) do	1			
Copper short tons	3	(7)	58	. (7)
Dry and siliceous (gold and silver) do	146, 811	lờ	140, 739	(7)
		000	21	m
Pebbles for grinding do	1	1	(1)	(1)
Pebbles for grinding do do detroleum barrels	493, 209, 000	494, 000, 000	505, 572, 000	568, ÒÓO, OO
Pumiceshort tons_	100, 200, 000	,,	(1)	(1)
alt (sodium chloride)do	402, 165	792, 214	656, 569	1, 713, 50
and and graveldo	6, 930, 975		12, 134, 312	6, 681, 27
liling (anarta)	0, 500, 510	0, 110, 000	1, 485	14.34
ilica (quartz) do ilver troy ounces	1, 326, 150	943, 040		
odium sulfate (natural)	(1)	(1)	75, 029	957, 35
tonedo	2, 737, 690		3, 497, 720	2, 908, 36
tonedo	2, 131, 090	2, 001, 000	1,959	31, 29
trontium mineralsdo		32, 143, 480	2, 842, 988	
ulfurlong tons		02, 140, 480	2, 842, 988	45, 487, 800 1, 500 (¹)
ulfur oredo	44	1,800		1, 50
ripolishort tons_	(1)	(1)	(1)	(1)
Tipoli short tons do	(1)	(1)		
Miscellaneous 8		1, 111, 009		7, 089, 640
Total value, eliminating duplications		725, 005, 009		868, 082, 69

### Mineral production of Utah, 1940-41

	19	940 1941		<b>L</b>	
Product	Quantity	Value	Quantity	Value	
Arsenious oxide short tons. Asphalt (native) do do	(1) 32,000	(¹) \$776, 171	(¹) 36, 476	(¹) \$856, 966	
Bismuthpounds	32,000 (2)	(2)	(2)	(2)	
Bitumen, natural sulfonatedshort tons	(i)	(1)	(1)	(1)	
Cement barrels Clay:	(1)	(1)	(1)	(1)	
Products (other than pottery and refractories)		<sup>8</sup> 630, 523		<sup>3</sup> 758, 000	
Raw (sold by producers)short tons	27, 506	98, 153	25, 366	54,019	
Coaldo	4 3, 575, 586	47,871,939	4 4, 076, 779	4 9, 509, 973	
Coke do Copper pounds	226, 347 463, 728, 000	(1 5) 52, 401, 264	246, 851 533, 676, 000	(1 5) 62, 973, 768	
Fluorsparshort tons	142	(1)	748	(1)	
Fuller's earthdodo			(1)	(1)	
Gems and precious stonestroy ounces	355, 494	(°) 12, 442, 290	356, 501	(6) 12, 477, 535	
Gypsum (crude)short tons	45, 421	60.055	61, 813	78, 147	
Iron:	·		-	•	
Oredo	365, 680	(1) (1 5)	397, 607	(1) (1 5)	
Pigdo Leaddo	(1 5) 75, 688	7, 568, 800	(1 s) 69, 601	7, 934, 514	
Limedo	49, 413	306, 357	56, 221	352, 306	
Magnesitedo			(X)	(1)	
Manganese oredodododo	30 2,354	(1) 13, 134	8	(1)	

<sup>1</sup> Value included under "Miscellaneous."
2 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
3 According to Bituminous Coal Division; value includes selling expenses.
4 No canvass.
5 Figures cover fiscal year ended June 30 of year stated.
6 Figures not available.
7 Not valued as ore; value of recoverable metal content included under the metals.
8 Includes minerals indicated by "!" above.

## Mineral production of Utah, 1940-41—Continued

Product	19	<b>4</b> 0	19	41
	Quantity	Value	Quantity	Value
Mercury	71, 472 1, 899, 563 12, 172, 299 (1) 1, 024, 660 (1) (1 5)	\$9, 374 (1) 1,063,000 28,000 (7) (7) (7) (7) (7) (7) (9) 3,000 (1) 191, 263 582, 708 8, 655, 857 (1) 693, 127 (1) (1,5)	(1) (1) (5, 562, 000 808, 000 30, 444, 402 622, 650 77, 979 5, 276 2, 302 708, 864 1, 344 4, 000 1, 340 (1) 107, 079 2, 760, 025 11, 395, 485 (4) 408, 140	(1) (1) \$1,145,000 45,000 (7) (7) (7) (7) (7) (7) (7) (7) (7) (7)
Vanadium pounds. Zine short tons. Miscellaneous 9.	169, 912	(1) (1) 5, 517, 288 10, 431, 709	(1) (1) <b>42, 049</b>	6, 307, 350 16, 096, 221
Total value, eliminating duplications		104, 392, 989		122, 386, 473

A Company of the Comp

1 Value included under "Miscellaneous,"

<sup>3</sup> Figures not available.

<sup>3</sup> 1940: Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

<sup>4</sup> According to Bituminous Coal Division; value includes selling expenses.

<sup>5</sup> Value not included in total value for State.

No can wass.
Not valued as ore; value of recoverable metal content included under the metals.
From copper smelting.
Includes minerals indicated by "1" above.

# Mineral production of Vermont, 1940-41

Product	1940		1941	
Product	Quantity	Value	Quantity	Value
Asbestosshort tons_	(1)	(1)	(1)	(1)
Products (other than pottery and refractories) Raw (sold by producers) Short tons Cobalt pounds	(1)	(1 2) (1)	(¹) 1, 399	(1 2) (1) (1)
Garnet, abrasive short tons tone do Mica, scrap do	(1) 61,026 290	(1) \$430, 178 2, 964	67, 824	(1) \$479, 21
Mineral watersgallons sold Nickelshort tons	(3)	(3)	(1)	(3) (1)
Sand and graveldodo	4 873, 325	4 217, 661 1, 555, 230	4 601, 918	4 127, 14 1, 921, 92
Stoneshort tons  Falcdo  Miscellaneous 6	<sup>8</sup> 135, 680 38, 516	\$ 3,681,752 423,368 668,619	185, 840 57, 248	4, 190, 11 663, 46 749, 79
Total value, eliminating duplications		6, 979, 772		8, 131, 6

<sup>1</sup> Value included under "Miscellaneous."

<sup>2</sup> 1940: Figures obtained through cooperation with Bureau of the Census; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

\*\*No canvass.

4 "Government-and-contractor." Value of "Commercial" included under "Miscellaneous."

5 Exclusive of crushed sandstone, value for which is included under "Miscellaneous."

6 Includes minerals indicated by "1," "4," and "9" above,

いっていませんである

### Mineral production of Virginia, 1940-41

	19	940	19	1941	
Product	Quantity	Value	Quantity	Value	
Aplite (crude) long tons. Barite short tons.	(1)	(1)	(1)	(1)	
Barite short tons	1 71	一流	M	K	
Cauxitedo	一流	l M	l M	X	
Cementbarrels	l is	l is	(1)	X	
Clay:	· · ·	1			
Products (other than pottery and refractories)		2 \$2,602,000		2 \$3, 369, 000	
Raw (sold by producers)short tons	(1)	(1)	(1)	40,000,000	
Coal do do	<sup>(1)</sup> 3 15, 348, 075	3 29, 965, 943	* 18, 440, 946	3 42, 917, 454	
Cokedo	198, 379	943,753	324, 573	4 1, 922, 181	
Feldspar (crude)long tons	21, 705	116, 531	(1)	(1)	
Ferro-alloys short tons	(14)	(14)	(1)	dia .	
Goldtroy ounces_	458	16,030	240		
Gypsum (crude) short tons				8, 400	
Iron:	(1)	(1)	(1)	(1)	
Oredo	(1)	(1)	371	(1)	
Pigdo	(i i)	(ì 4)	(14)	(14)	
Kyanitedodo	(1)	(1)	5, 461	116, 952	
Leaddodo	2, 285	228, 500	3, 390	386, 460	
Lime do	178, 036	1,044,229	224, 293	1, 359, 281	
Manganese oredo	2, 482	41, 286	(1)	1,000,201	
Manganiferous oredo	5, 106	* 30, 069	\ \i		
Marl, calcareous do	8, 176	7, 392	24, 113	23, 169	
Mica:	0, 170	1,002	24, 110	25, 109	
Scrapdo	71)	70	(1)	an a	
Sheetpounds	(1) (1)	l X	(1)	1 13	
Millstones	(9)	X	(-)	1 13	
Mineral waters gallons sold		12		1 (2)	
Natural gas	(5) 80,000	(5) 81,000	(5) 106, 000	(5) 94, 000	
Ores (crude), etc.:	80,000	81,000	106,000	94,000	
Dry and siliceous (gold and silver)_short tons					
Dry and sinceous (gold and shver)_short tons	2, 480	(6)	540	(9)	
Zincdo			35	(6)	
Zinc-leaddo	599, 759	(6) (1)	501, 555	(6)	
Phosphate rock long tons	(1) (1)	(1)	(1) (1)	(1)	
Pyritesdo	(1)	(1)	(1)	(1)	
Saltshort tons	(1)	(1)	(1)	(1)	
Sand and graveldodo	2, 671, 412	1, 778, 576	4, 593, 193	3, 770, 650	
Sand and sandstone (ground) do	(1)	(1)	(1)	(1)	
Bilica (quartz)do	(1)	(1)			
Silvertroy ounces	271	193	135	96	
Slate		(1)		(1)	
Stone 7short tons	6, 890, 640	6, 959, 136	9, 195, 450	9, 586, 541	
Talc and ground soapstone 7do	(1)	(1)	(1)	(1)	
	`'	, 😯			
Ilmenitedo	(1)	(1)	: (1)	. (1)	
Rutiledo	71	Ж	K	Ж	
Zincdodo	16,927	2, 132, 802	22, 913	3, 436, 950	
Miscellaneous 8	10, 021	10, 966, 418	22, 313	12, 083, 722	
		10, 500, 210		14, 000, 144	
Total value, eliminating duplications		50, 003, 672		71, 340, 934	
		JU, JUO, J/Z		11. 34U. 934	

<sup>1</sup> Value included under "Miscellaneous."

2 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.

3 According to Bituminous Coal Division; value includes selling expenses.

4 Value not included in total value for State.

5 No canvass.

6 Not valued as ore; value of recoverable metal content included under the metals.

7 Soapstone used as dimension stone included in figures for stone.

8 Includes minerals indicated by "1" above.

# Mineral production of Washington, 1940-41

생활 경기 교회를 잃었다면 사람들이	19	40	194	1
Product	Quantity	Value	Quantity	Value
Aluminum short tons Antimony ore (concentrates) do do	4, 994	1 \$1, 823, 000	(1 2) (2)	(1 2) (2)
Arsenious oxide do Cement barrels	(3)	(3) (2)	(2) (3) (2)	(3) (2)
Clay: Products (other than pottery and refractories) Raw (sold by producers) Short tons Coal do	35, 915 5 1, 650, 352	4 1, 241, 000 47, 353 5 5, 221, 717	81, 534 5 1, 841, 274	4 \$1, 132, 000 103, 737 5 6, 478, 674
Coke         do           Copper         pounds           Diatomite         short tons           Ferro-alloys         do		2, 172, 312 (²)	17, 372, 000 (2) (1 2)	2, 049, 896 (2) (1 2)
Fluorspar do Gems and precious stones troy ounces.	82, 136	(6) 2,874,760	104 84, 176	(2) (6) 2, 946, 160
Graphite, crystalline pounds. Iron oré short tons. Lead do. Lime do. Megraeite do.	6, 252 2, 555 53, 428	(2) 255, 500 582, 416 (2)	(2) 7, 271 3, 903 62, 309 (2)	(2) (2) 444, 942 656, 363 (2)
Magnesium sulfate (natural) pounds.  Manganese ore short tons.  Manganiferous ore do.  Mercury flasks (76 pounds)  Mineral waters gallons sold		(2) (2) (6)	(2) (3) (6)	ම ල ල ල
Molybdenum pounds Mouhic feet	4, 624 36, 000	(2) 37,000	1,000	2,000
Ores (crude), etc.: Copper. short tons. Dry and siliceous (gold and silver) do Lead do Zinc-lead do Peat do	689, 325 204, 146 100 273, 227 (2)	(f) (f) (7) (2)	694, 565 180, 700 152 363, 092 (2)	<u> </u>
Pulpstones do Sand and gravel do Sand-lime brick thousands of brick Silver troy ounces	180 6, 987, 761 (2 8) 365, 175	11, 130 4, 278, 251 (2 8) 259, 680	150 5, 583, 285 (8) 402, 030	16, 065 2, 476, 834 (8) 285, 888
Stone short tons Strontium minerals do Tale and ground soapstone do Tungsten ore (60-percent concentrates) do	2, 347, 190 (2) 4 74	1, 941, 820 (2) 1, 394 (2) 1, 456, 560	2, 148, 970 (2) 6 (2) 14, 320	1, 757, 873 (2) 2, 426 (2) 2, 148, 000
Zinedo	11,500	7, 709, 823	14, 320	30, 662, 278
Total value, eliminating duplications		28, 090, 188		28, 507, 28

¹ Value not included in total value for State.
² Value included under "Miscellaneous."
³ Figures not available.
⁴ 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
⁵ According to Bituminous Coal Division; value includes selling expenses.
⁵ No canvass.
² Not valued as ore; value of recoverable metal content included under the metals.
⁵ 1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canvass by Bureau of the Census and no estimate made.
⁵ Includes minerals indicated by "³" above.

# Mineral production of West Virginia, 1940-41

			·	
	19	140	1941	
Product	Quantity	Value	Quantity	Value
Bromine pounds Calcium chloride short tons Cement barrels Clay:	1, 152, 237 12, 103 (¹)	\$179, 011 79, 978 (¹)	1, 048, 178 13, 234 (¹)	\$206, 768 71, 832 (¹)
Products (other than pottery and refractories) Raw (sold by producers)short tons Coaldo	55, 853 3126, 437, 621	2 2, 451, 000 103, 989 3 231, 603, 534	70, 885 3 140, 250, 248	3 3, 180, 000 133, 300 3 313, 255, 559
Cokedo Ferro-alloysdo Grindstones and pulpstonesdo	2, 133, 003 (1 4) 4, 604	4 6, 170, 849 (1 4) 207, 044	2, 245, 307 (1 4) 2, 090	4 7, 626, 823 (1 4) 102, 562

See footnotes at end of table.

大人の大学を大学を大学を大学

## Mineral production of West Virginia, 1940-41—Continued

	19	940	1941		
Product	Quantity	Value	Quantity	Value	
Iron, pig short tons Lime do Magnesium chloride (natural) pounds	941, 299 278, 300	\$1, 727, 844	1, 032, 148 372, 677	(1 4) \$2,350,362	
Manganese ore short tons Manganiferous ore do	245	(1)	(1)	(i)	
Marl, calcareous do Millstones	(1)	(1)	(1)	(i)	
Mineral waters gallons sold Natural gas M cubic feet	188, 751, 000	(5) 76, 065, 000	207, 681, 000	(5)	
Natural gasoline and allied products:		70,000,000	201, 081, 000	81, 957, 000	
Natural gasoline gallons Liquefied petroleum gases do	58, 782, 000	1, 848, 000 (6)	65, 873, 000 32, 171, 000	2, 717, 000 1, 354, 000	
Petroleumbarrels_	3, 444, 000	6, 400, 000	3, 433, 000	7, 390, 000	
Rubbing stones short tons Salt dodo	144, 312	701, 953	143, 780	(1)	
Sand and graveldo	2, 297, 610	2, 240, 650	2, 733, 607	792, 104 3, 185, 639	
Sand and sandstone (ground)do	_ (1)	(1)	(1)	(1)	
Stonedo	7 3, 719, 950	7 3, 818, 788	7 4, 547, 200	7 5, 988, 840	
Miscellaneous 9	-	31, 257, 639	(1 4)	(1 4) 48, 275, 238	
Total value, eliminating duplications		329, 891, 960		425, 626, 303	

1 Value included under "Miscellaneous."

No canvass

# Mineral production of Wisconsin, 1940-41

Product	19	140	1941	
Product	Quantity	Value	Quantity	Value
Cementbarrels_	(1)	(t)	(1)	(1)
Clay: Products (other than pottery and refractories)		2 \$326,000		2 \$578, 000
Raw (sold by producers)short tons	(1 8)	(1 8)	(1) (1 8)	(1) (1 3)
Iron ore— Sold to furnacesdodo	1, 375, 181	3, 290, 389	1, 665, 189	3, 998, 287
Sold for paintdododo	670 445	(1) 44, 500	1, 225	139, 650
Lime do do Marl, calcareous do Mineral waters gallons sold	65, 632 (1) (4)	542,749 (1)	79,077 (¹)	659, 324 (¹)
Ores (crude), etc.:			` `	(4)
Zinc-leaddo	190, 326	(5)	157, 068 54, 905	(b) (5)
Peatdodo			(1)	(1)
Pyriteslong tons Sand and gravelshort tons	(1) 6, 742, 882	(¹) 2, 304, 197	(1) 9, 263, 237	(1) 3, 398, 039
Sand and sandstone (ground)dodo	(1)	(1)	(1)	3, 390, 039 (1)
Sand-lime brickthousands of brickshort tons	(1 6)	(1 b) (1)	8	(6)
Stone do do do	4, 330, 360 5, 770	5, 030, 263 727, 020	4, 376, 720 6, 238	5, 666, 120 935, 700
Miscellaneous 7		5, 356, 657	0, 200	6, 830, 786
Total value, eliminating duplications		13, 553, 683		17, 020, 722

Yaute instance unter index instances.
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 According to Bituminous Coal Division; value includes selling expenses.
 Value not included in total value for State.

<sup>Figures not available.
Exclusive of dimension limestone in 1940 and of dimension sandstone in 1941, value for which is included under "Miscellaneous."
From zine smelting.
Includes minerals indicated by "1" and "7" above.</sup> 

Value included under "Miscellaneous."
 1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
 Value not included in total value for State.

<sup>Value not mentated in 5 cm.
No canyass.
Not valued as ore; value of recoverable metal content included under the metals.
1940: Figures obtained through cooperation with Bureau of the Census; 1941: No canyass by Bureau of the Census and no estimate made.
7 Includes minerals indicated by "1" above.</sup> 

# Mineral production of Wyoming, 1940-41

	19	40	1941	
Product	Quantity	Value	Quantity	Value
Beryllium concentratesshort tonsbarrels	(1)	(¹) 2 \$193,000	(1)	(1) (1) 2 \$194,00
Raw (sold by producers)snort tons	91, 714	976, 844	145, 574 6, 646, 330 8, 000	1, 369, 05 13, 916, 22 94 43, 48
Coal	740 5, 415 931, 072	(4) 25, 900 8, 393 (1)		(i) (i)
Mineral watersgallons sold Natural gas M cubic feet Natural gasoline and allied products: Natural gasoline gallons Liquefied petroleum gases do	27, 346, 000 33, 380, 000 ( <sup>5</sup> )	5, 221, 000 1, 271, 000 (5)	29, 284, 000	
Ores (crude), etc.:  Coppershort tonsdobarrelsshort tons.  Petroleumbarrelsshort tonsshort tons	30 783	(6) (6) 20, 600, 000	42 117	(°) (°) 25, 700, 00 840, 93
ilver try ounces	(1) 405, 140	(1) 375, 463	(1) 94	(1) 737, 4! 21
Vermiculiteshort tons Miscellaneous T Total value, eliminating duplications		1, 833, 900		2, 307, 23 52, 751, 35

The second secon

<sup>1</sup> Value included under "Miscellaneous."
1940: Estimate by Bureau of Mines based on figures issued by Bureau of the Census as somewhat incomplete; 1941: Estimate by Bureau of Mines as no general canvass by Bureau of the Census.
2 According to Bituminous Coal Division; value includes selling expenses.
3 No canvass.
3 Figures not available.
6 Not valued as ore; value of recoverable metal content included under the metals.
7 Includes minerals indicated by "1" above.

# PART II. METALS

# GOLD AND SILVER

By C. E. NEEDHAM

### SUMMARY OUTLINE

	Page		Page
General summary	79	Mine report—Continued.	- 450
Salient statistics	80	Mine production—Continued.	
Government regulations and their effects	80	Ore production, classification, metal yield.	
Domestic refinery production	85	and mathods of recovery	100
Prices of gold and silver	86	Placers	103
United States and world monetary stocks	87 1		
Consumption and uses	88	Other placer-mining methods	106
Imports and exports	89	Employment and production	107
Domestic supply	91	World aspects	118
Mine report		World production	118
Method of collecting statistics	92	Review by countries	122
Units of measurement	92	Canada	122
Mines producing	92	Mexico	123
Leading gold producers	92	Central America	124
Leading silver producers	93	South America	124
Number of mines	95	Africa	126
Mine production	96 96	Oceania	126
Dummar v	UK I		

### GENERAL SUMMARY

Gold and silver, beset by regulations, labor shortages, and economic factors, made a poor showing in many countries in 1942, and output in the United States dropped to the lowest quantity since 1935. World production of gold slumped an estimated 10 percent and silver about 5 percent from 1941, although information from many foreign countries on both metals is so scanty that many estimates have little value. Output of gold in North America declined about 16 percent. Production in the United States was reduced 26 percent, Canada 10 percent, and Newfoundland 26 percent; Mexico, however, reported a very slight increase. South America recorded a decrease of about 10 percent. The world's greatest gold-producing nation, the Union of South Africa, maintained its production at a high figure in spite of difficulties, and output decreased only about 2 percent.

Silver output in the United States dropped less in proportion than gold but dropped 21 percent from 1941. The increased tonnage of base-metal ores maintained production of silver better than of gold. Production in Canada held up well, and output differed but little from 1941; in Mexico it increased over 8 percent and climbed to the highest figure since 1931. Production in Central and South America remained much as in 1941; in fact, South America is believed to have made a slight increase. Output in the Western Hemisphere as a

whole decreased about 5 percent.

Salient statistics of gold and silver in the United States, 1925–29 (average) and  $1939\!-\!42^{\,1}$ 

	Average (1925–29)	1939	1940	1941	1942
Mine production,					
ounces:	2, 170, 798	4, 673, 042	4, 869, 949	4, 750, 865	3, 457, 110
Silver	61, 511, 087	64, 373, 281	70, 549, 362	67, 258, 997	54, 090, 765
Number of mines pro-					
ducing gold and sil-					
ver:	2, 187	5, 354	5, 393	4, 542	2, 619
Lode Placer	1, 243	4,036	4, 176	3,349	1,758
Ore produced, short	-,	<b>-,</b>			
tons:			** *** ***		0 407 007
Gold ore	7, 014, 646	16, 886, 630	16, 550, 095	15, 117, 117 1, 447, 371	9, 487, 907 1, 163, 970
Gold-silver ore	597, 075	1, 212, 734 1, 367, 164	948, 171 1, 201, 469	1, 074, 543	996, 823
Silver ore Percentage derived	799, 061	1, 307, 104	1, 201, 100	1,011,010	000,020
from—					
Dry and siliceous					
ores:		20	E0	54	50
Gold	57 21	60 47	56 41	41	37
Silver	21	*1	24	**	•
Base metal ores: Gold	23	12	13	14	21
Silver	79	53	58	59	62
Placers:				31	29
Gold	20	29	(2)	(3)	(2)
Silver	(2)	(2)	()	(4)	<b>.</b>
Net industrial con- sumption: 3			100		
Gold, dollars	27, 938, 073	7, 460, 600	13, 306, 032	37, 001, 620	47, 294, 810
Silver, ounces	28, 747, 779	44, 613, 005	44, 498, 903	72, 432, 318	101, 398, 695
Imports, dollars:	001 001 000	0 774 650 040	4, 749, 467, 203	982, 442, 027	315, 779, 716
Gold	201, 971, 673 64, 264, 486	3, 574, 658, 840 85, 307, 095	58, 433, 866	47, 053, 413	41, 103, 149
SilverExports, dollars:	04, 204, 400	00,001,000	00, 200, 000		
Gold	251, 428, 995	508, 063	4, 994, 899	64, 280	102, 126
Silver	87, 559, 828	14, 629, 792	3, 674, 385	5, 673, 361	1, 999, 490
Monetary stocks:				22, 737, 000, 000	22, 726, 000, 000
Gold, dollars	4, 339, 000, 000	17, 644, 000, 000 2, 927, 000, 000	21, 995, 000, 000 3, 135, 000, 000	3, 280, 000, 000	3, 334, 000, 000
Silver, ounces	1, 417, 000, 000	2, 921, 000, 000	3, 130, 000, 000	0,200,000,000	0,002,000,000
Price, average, dollars per ounce:	A 1 4 4				
Gold	20.67+	35, 00	35.00	35, 00	35.00
Silver	.600+	.678+	.711+	.711+	.711-
World production,					
ounces: 3	18, 988, 557	39, 534, 430	41, 067, 101	40, 332, 204	37, 000, 000
GoldSilver	254, 377, 085	265, 926, 968	272, 510, 428	262, 854, 226	249, 663, 000

<sup>1</sup> Philippine Islands and Puerto Rico excluded.

# GOVERNMENT REGULATIONS AND THEIR EFFECTS

Gold.—The marked slump in gold output in the United States in 1942 was traceable to the effects of the war program. Even as early as 1941, labor began to leave the mines to seek higher wages in defense industries, and the movement became much more pronounced in 1942. Another factor in the decreased production was the order from the War Production Board early in 1942 that excluded gold and silver mines from the priority benefits of Preference Rating Order P-56. Thus, shortages of labor and equipment, coupled with increased taxes and fixed prices for gold and silver, were already rapidly forcing down production late in 1941 and early in 1942.

On October 8, 1942, the War Production Board issued its Limitation Order L-208, the essential part of which reads as follows:

Less than 0.5 percent.
 U. S. Bureau of the Mint, except Bureau of Mines estimate for 1942 world production.

<sup>(</sup>a) Definitions.—For the purposes of this order (1) "Nonessential mine" means any mining enterprise in which gold is produced, whether lode or placer, located

in the United States, its Territories or possessions, unless the operator of such mining enterprise is the holder of a serial number for such enterprise which has

been issued under Preference Rating Order P-56.

(2) With respect to any nonessential mine, "effective date" means October 8, 1942, or the date of cancellation by the Director General for Operations of the

serial number for such mining enterprise, whichever is the later.

(b) Restrictions upon production.—(1) On and after the effective date, each operator of a nonessential mine shall immediately take all such steps as may be necessary to close down, and shall close down, in the shortest possible time, the operations of such mine.

(2) In no event on or after seven days from the effective date shall any operator of a nonessential mine acquire, consume, or use any material, facility, or equipment to break any new ore or to proceed with any development work or

any new operations in or about such mine.

(3) In no event on or after sixty days from the effective date shall any operator of a nonessential mine acquire, consume, or use any material, facility, or equipment to remove any ore or waste from such mine, either above or below ground, or to conduct any other operations in or about such mine, except to the minimum amount necessary to maintain its buildings, machinery, and equipment in repair and its access and development workings safe and accessible.

(4) The provisions of this order shall not apply to any lode mine which produced 1,200 tons or less of commercial ore in the year 1941, provided the rate of production of such mine, after the effective date, shall not exceed 100 tons per month, nor to any placer mine which treated less than 1,000 cubic yards of material in the year 1941, provided that the rate of treatment of such placer mine, after the effective date, shall not exceed 100 cubic yards per month.

The Board also asked the mines affected to submit complete data covering the minimum number of workers and the minimum quantity of critical materials needed to keep the mines on a basis sufficient to pay stand-by expenses, together with information on the ages of employees and whether stand-by operations could be maintained

with men above military age.

On November 25, Order L-208 was amended so that equipment of types listed on Schedule A, Order P-56, could no longer be sold without permission from the War Production Board, and the equipment was to be inventoried and reported by January 15, 1943, or within 60 days after revocation of a P-56 serial number. submitted were to indicate the prices of machinery that the owner was willing to sell or rent so that the Board could distribute the available units to other mines where the output of needed metals could be considerably increased.

On December 8 the Board announced that regulations had been eased slightly so that a number of mines were granted permission to remove and mill broken ore or gravel with a small crew of men for 6 months, provided that such operations would not consume substantial amounts of critical materials and would employ only men who were not eligible for military service or not needed in mining opera-

tions elsewhere.

The avowed purpose of Order L-208 and its amendment was to provide additional manpower and equipment for mines producing metals more vitally needed than gold—particularly copper mines. To induce such a shift of labor the War Manpower Commission ruled that no former gold miner could obtain a new job west of the Mississippi without the approval of the United States Employment Service, and this Service was instructed to assign former gold miners only to nonferrous mining jobs, except in cases of undue hardship.
In 1941 Order L-208 would have affected over 250 lode mines and

possibly 700 placers in the United States and Alaska, operations that employed over 20,000 men. However, by October 1942 so many of these men had joined the armed forces or had gone into the numerous war industries that the number employed was very greatly reduced. Of those remaining, many for various reasons were unsuited to be transferred to other mining camps or were needed to maintain equip-

ment and properties during the closing period.

Order L-208 provoked much discussion, both for and against the order. One group contended vigorously that many gold-mining communities were isolated and their economic life was more vulnerable than that of industrial centers; that so few men could be made available for other work by the closing order that the cost would outweigh the gain; that the Government continued to supply gold miners in other countries and to buy their output while the gold mines in the United States were singled out from a host of industries regarded as nonessential and made the victims of direct action; and that gold miners and their families could contribute much greater net gain to

the war program under a much less drastic order.

The other group asserted with equal intensity that the order testified eloquently to the uselessness of gold as a means of financing our war program; that our continued acceptance of gold from South Africa, Canada, and Russia was due primarily to a desire not to disrupt the domestic economy of our Allies or to put additional obstacles in the way of their paying for needed American goods; that no such political expediency made it necessary to continue producing gold from domestic mines; that it was folly to waste manpower by extracting more gold from the earth and interring it in Government vaults; that localized disturbances to the domestic economy brought about by closing the gold mines would be severe but that they would be insignificant compared with the Nation-wide industrial dislocations resulting from conversions to a wartime basis; and that the closing of gold mines should be followed by increased production of critical metals so urgently needed for war materials.

Silver.—Gold did not stand alone with respect to regulation and heated discussion—silver came in for an even greater share, and scarcely a month went by that some action was not taken or attempted. Feeling ran high at times and was vigorously expressed on the floors of Congress, in committee rooms, through the press, and over the

radio.

Early in the year agitation became strong for silver to do its full share in the war, and to further this objective Secretary Morgenthau announced in February that he had recommended that all silver legislation be struck off the books to get silver into greater productive

service.

The Treasury Department held at this time about 47,000 tons (1,360,000,000 ounces) of "free" or unallocated silver—that is, silver not needed as coin or as a reserve against outstanding silver certificates, which, when lent, must be returned; it cannot be consumed. On April 7 the Attorney General ruled that the Treasury Department could legally issue this silver to war-production plants for nonconsumptive purposes, and on May 6 an agreement was made for leasing unpledged bullion to the Defense Plant Corporation and for delivering it as needed for manufacture into nonconsumable forms.

Silver was included under the General Maximum Price Regulation issued on April 28 by the Office of Price Administration, and the provision became effective May 11 for bullion and May 18 for articles

THE REPORT OF THE PARTY WAS IN THE PARTY OF THE PARTY OF

一人の大変ないない。 教がはまずいから

ASSESSED TO THE PARTY OF THE PA

sold at retail. But the ceiling price of 35% cents per ounce on bullion from foreign countries did not apply in Mexico, and soon considerable bullion was being purchased there at a substantial premium and

imported into the United States.

Increased demands by both essential and nonessential users and decline in supplies from normal sources soon created a shortage of the metal, so that early in July the Bureau of Industrial Conservation recommended that silver no longer be used as a substitute for other scarce metals. The situation rapidly became worse, and on July 21 silver was placed on the restricted list of imports by the War Production Board. Under this provision the private importation, sale, processing, or shipment of silver beyond the place of initial storage was prohibited, except by special authorization from the Board.

On July 29, the Board ruled (Conservation Order M-199) that after October 1 no foreign silver could be purchased or processed for certain nonessential civilian uses, except to fill orders with a preference rating of A-3 or higher. Also, from July 29 to October 1 no manufacturer might purchase or put into process for such restricted uses foreign silver in excess of 1 month's supply, based on his average consumption

for 1941 or the first half of 1942.

Effective August 10, the Office of Price Administration established a ceiling price of 35% cents an ounce on all imports of silver bullion. This attempt at price control proved unsatisfactory, so that another order was issued, effective August 31, whereby importers were authorized to pay up to 45 cents an ounce for Mexican silver. responding price increases, authorized in September, for all silver bullion, for semifabricated products containing silver, and for scrap silver established generally a price of 45 cents an ounce for foreign

Likewise, late in August the Office of Price Administration issued an order providing that semifabricating companies, makers of silver sheets, blanks, and similar articles, could pay the Treasury price of 71.11 cents an ounce for silver and pass the increased cost to the fabricating consumer; the previous price level had been fixed on a

basis of silver costing 35% cents an ounce.
On September 17 Secretary Morgenthau announced that the Treasury had 5,000,000 ounces of "silver ordinary," that is, silver not acquired under silver monetary legislation, which could be sold outright at 45 cents an ounce to industrial users with high priority ratings on recommendation of the War Production Board. Priority orders on

hand failed to absorb all this silver.

Demands for the release of Treasury silver continued to grow during The Silver Users Emergency Committee, formed early in September, was very active in influencing Congress and the public toward proposed legislation that would make available to both essential and nonessential industries the ample supply of Treasury silver not actually in the form of coinage. At no time, however, did the committee advocate repeal of the Silver Purchase Act.

The sentiments of certain groups were crystallized in a number of bills introduced in Congress late in 1942 and early in 1943. On September 14 Senator Green introduced a bill (S. 2768) designed to remove the restrictions on the use of silver after purchase in order that it might be used for consumptive as well as nonconsumptive purposes, provided that no silver was to be sold at less than its cost to the

United States or at less than the then current market price, whichever was higher; also, that the Government should maintain sufficient silver to cover all outstanding silver certificates. The Green bill was amended to include minor changes, but the Senate adjourned without passing the bill in any form. The Celler bill, introduced on September 17, proposed the repeal of all provisions of the Silver Purchase Acts of 1934 and 1939, but, like the Green bill, it failed to pass.

Several bills on silver legislation were offered in January 1943, among them the Green bill (S. 35), in much the same form as in 1942; the Celler bill (H. R. 823), essentially a Green bill for the House of Representatives; the Treadway bill (H. R. 102), calling for outright repeal of the Silver Purchase Acts; and the Murdock bill (S. 192), under which fabricators might purchase silver to be used exclusively for consumption purposes from stocks owned by the Government.

Frequent and heated arguments on the silver question came from the press and over the radio. One group took the stand that to continue to buy silver at prices above the world market for monetary purposes was so glaringly stupid that steps should be taken immediately to repeal the Silver Purchase Acts; that the orders on silver issued by the Office of Price Administration continued to maintain the subsidy to our silver mines by making semifabricators pay the subsidy themselves and pass the charge to the customers; that the orders increased the cost of silver to our armament industries; that they were a concession to the Mexican Government, which profited thereby because we failed to make proper use of the ample supply held by our own Treasury; that the Green bill was endorsed by the Treasury, the armed services, the War Production Board, and many others; that as a substitute for tin, copper, cadmium, nickel, aluminum, antimony, tungsten, and other metals, the Government silver hoard was a valuable stock pile but kept by the Treasury this hoard was useless; that used in airplane and other engines this silver would help sweep the Japanese from the seas; in vital parts for tanks and trucks, it would help annihilate Hitler; but buried at West Point, it was a monument to folly.

The other group stoutly held that the enemies of silver were seeking to use the intrinsic value of the metal for war purposes as a vehicle to strike down silver as money; that history teaches that silver is the oldest and best monetary metal and that it is the only legal money of the United States today; that as an economic weapon at the peace table, our great supply of silver will be equally as potent as in war; that an abundance of silver had been coming on the market to meet the demands of American war industries; that complaints of insufficient silver came not from war industries but from manufacturers of nonessential articles who were out to make a larger profit in advocating the enactment of a law that would give them the privilege of buying United States Treasury silver that was acquired solely for use as money; and that so much silver is now a byproduct of base-metal mining that to lower the price of silver would deal a serious blow to the economic stability of the base-metal mining industry.

### DOMESTIC REFINERY PRODUCTION

The figures in the following table were obtained through cooperation between the United States Bureau of the Mint and the Bureau of Mines and were agreed upon after conference and adjustment

between the two Bureaus.

The State totals are based upon bullion deposits in the United States mints and assay offices and upon returns to the Bureau of the Mint from smelting and refining companies. The State distribution is adjusted further by the Bureau of Mines from its geographical records of sources and production, both historical and current, from the producing mines and is tabulated for the mine reports discussed later. The data for the total production and in part for the distribution are obtained from records of (1) the unrefined domestic gold and silver deposited in the United States mints and assay offices; (2) the domestic gold and silver in fine bars reported by private refineries, supplemented by data of content of unrefined mattes, blister copper, copper anodes, and lead bullion; and (3) the unrefined domestic gold and silver contained in ore and matte exported for reduction. The last item is small.

Gold and silver produced in the United States, 1938–42, and approximate distribution of source, by States and Territories, in 1942

[Refinery figures supplied by U. S. Bureau of the Mint	Refinery	figures sur	oplied by	U. S.	Bureau of	the Mint
--	----------	-------------	-----------	-------	-----------	----------

	G	old 1	Silver 2	
State or Territory	Fine ounces	Value	Fine ounces	Value
1938	5, 089, 811	\$178, 143, 400	62, 665, 335	\$40, 510, 92
939	5,611,171	196, 391, 000	65, 119, 513	44, 202, 27
940		210, 108, 700	69, 585, 734	49, 483, 18
941		209, 174, 600	72, 336, 029	51, 438, 95
942:				
942: Alabama	_ 1	35	l	
Alaska	503,040	17, 606, 400	143, 100	101, 76
Arizona		8, 978, 235	6, 982, 808	4, 965, 55
California		31, 295, 180	1,480,560	1, 052, 84
Colorado		10, 136, 805	3, 964, 072	2, 818, 89
Georgia		945	3	
Idaho	98,795	3, 457, 825	14, 195, 091	10, 094, 28
Illinois		-,,	283	20
Michigan			54, 227	38, 56
Missouri			27, 533-	19, 57
Montana	156, 557	5, 479, 495	10, 897, 784	7, 749, 53
Nevada		10, 495, 660	4, 339, 118	3, 085, 59
New Mexico	17,446	610, 610	893, 360	635, 27
New York		0-0,0-0	37, 306	26, 52
North Carolina	4,396	153, 860	8, 297	5, 90
Oregon	50,718	1, 775, 130	137, 947	98, 09
Demonstrania		92, 680	18, 577	13, 2
Pennsylvania Philippine Islands	158,726	5, 555, 410	231, 197	164. 40
Court Consider	8, 102	283, 570	5, 254	3, 7
South Carolina	535, 461	18, 741, 135	192, 121	136, 6
Tennessee	129	4, 515	33, 161	23, 5
Texas		9, 695	791, 039	562, 5
		13, 674, 500	11, 276, 521	8, 018, 8
Utah		3, 465	31	0,010,0
Virginia		2, 606, 835	381, 458	271, 2
Washington Wyoming	35	1, 225	7	211,20
11 J. O. T.				
	3,741,806	130, 963, 210	56, 090, 855	39, 886, 83

Gold valued at \$35 a fine ounce.
 Silver valued as follows: 1938, \$0.646+; 1939, \$0.678787+; 1940-42, \$0.7111+.

### Gold and silver produced in the United States, 1792-1942

[From Report of the Director of the Mint. The estimate for 1792-1873 is by R. W. Raymond, commissioner of mining statistics, and since then by the Director of the Mint]

D.J. 3	G	old	Silver		
Period	Fine ounces	Value 1	Fine ounces	Value 2	
1792–1847 1848–72 1873–1942	1, 187, 170 58, 279, 778 211, 700, 035	\$24, 537, 000 1, 204, 750, 000 4, 982, 088, 500	309, 500 118, 568, 200 3, 666, 522, 549	\$404, 500 157, 749, 900 2, 755, 210, 678	
	271, 166, 983	6, 211, 375, 500	3, 785, 400, 249	2, 913, 365, 078	

<sup>1</sup> Gold valued in 1934 and thereafter at \$35 per fine ounce; prior thereto at \$20.67+per fine ounce. Dollar

The average commercial value per fine ounce of silver for the total recorded domestic production is \$0.770.

### PRICES OF GOLD AND SILVER

Gold.—Under the Gold Reserve Act of 1934 the value of gold was fixed by Presidential proclamation on January 31, 1934, at \$35 per fine troy ounce and has remained at that figure through 1942. From

Price of silver in London and in New York, 1941-42

[From the Report of the Director of the Mint]

	London price per ounce, 0.925 fine				United States equivalent.	Average monthly New York
Month	Highest	Lowest	Average	Average monthly exchange, New York on London	per fine ounce, of London price, at current rate of ex- change	price of fine bar silver, per ounce (mean of bid and asked quo- tations)
January February March April May June July August September October November December	Pence 23% 23% 23% 23% 23% 23% 23% 23% 23% 23%	Pence 23/16	Pence 23. 2727 23. 3406 23. 4464 23. 5000 23. 4574 23. 4000 23. 3967 23. 4594 23. 5000 23. 5000 23. 5000 23. 5000	Dollars 4. 0342 4. 0297 4. 0319 4. 0248 4. 0310 4. 0316 4. 0323 4. 0318 4. 0327 4. 0329 4. 0342 4. 0342 4. 0350	Dollar 0. 42291 . 42367 . 42582 . 42605 . 42593 . 42496 . 42496 . 42604 . 42688 . 42690 . 42704 . 42713	Dollar 0. 35062 35062 35062 35062 35062 35062 35062 35062 35062 35062 35062 35064 35064 35084 35437
January 1942 February March April May June July August Septamber October November December	23/4 23/4 23/4 23/4 23/4 23/4 23/4 23/4	23½ 23½ 23½ 23½ 23½ 23½ 23½ 23½ 23½ 23½	23, 5000 23, 5000 23, 5000 23, 4970 23, 5000 23, 5000 23, 5000 23, 5000 23, 5000 23, 5000 23, 5000 23, 5000	4. 0350 4. 0350 4. 0348 4. 0350 4. 0350 4. 0350 4. 0350 4. 0350 4. 0350 4. 0350 4. 0350	. 42713 . 42713 . 42711 . 42707 . 42713 . 42713 . 42713 . 42713 . 42713 . 42713 . 42713 . 42713	. 35437 . 35437 . 35437 . 35437 . 35437 . 35437 . 45062 . 45062 . 45062
Average, calendar year 1941 Average, calendar year 1942	- 1		23. 4390 23. 4998	4. 0318 4. 0350	. 42568 . 42713	. 35095 . 38645

figures are rounded.

3 Silver valued in 1934 and thereafter at Government's average buying price for domestic product: In 1934 and 1938 at \$0.64+per fine ounce, in 1935 at \$0.71875, in 1936 at \$0.7745, in 1937 at \$0.7735, in 1939 at \$0.678787+, and in 1940-42 at \$0.7111+.

THE REPORT OF THE PARTY OF THE

January 18, 1837, through 1932, the price was \$20.67+ per ounce, and in 1933 the legal coinage value was continued at \$20.67+. The average weighted price per fine ounce in 1933, as computed by the Bureau of Mines, was \$25.56 and in 1934, \$34.95. A complete account of regulations pertaining to gold and silver in 1933–34 is given in the chapter on Gold and Silver in Minerals Yearbook, 1934 (pp.

25-46), issued by the Bureau of Mines.

Silver.—The Government price for newly mined domestic silver was maintained throughout 1938 and to June 30, 1939, at \$0.64646464+ per fine ounce. The act of Congress approved July 6, 1939, fixed the price of domestic silver mined after July 1, 1939, at \$0.711+ per ounce. The annual average prices 2 used for domestic silver from 1932 to 1939 are as follows: 1932, \$0.282; 1933, \$0.350; 1934, \$0.646464646+; 1935, \$0.71875; 1936, \$0.7745; 1937, \$0.7735; 1938, \$0.646464646+; 1939, \$0.678787878+; 1940-42, \$0.711111111+.

# UNITED STATES AND WORLD MONETARY STOCKS

According to figures published in the Federal Reserve Bulletin, the gold reserves of the United States totaled \$22,726,000,000 at the end of 1942, a decline of \$11,000,000 during the year. This reversal of trend was caused by net sales to foreign countries exceeding the flow

of domestic gold.

Figures are not available for the gold reserves held at the end of 1942 by central banks and governments in many other countries of the world. However, by using the data available for 1942 and making certain assumptions based on the latest figures available for past years, it is believed that the total reserves of the world amount to approximately \$33,000,000,000, including stabilization funds. On this basis, the reserves of the United States constitute about 70 percent of the world total.

United States Treasury silver holdings at the close of 1942 approximated 3,334,000,000 ounces, a gain of about 54,000,000 ounces over 1941. The holdings for 1942 represent nearly 115,000 tons of the

metal.

The Twenty-seventh Annual Review of the Silver Market, 1942, by Handy & Harman, contains the following paragraphs regarding silver purchases and coinage:

At the end of the year gold holdings of the United States were practically unchanged from the 1941 closing figures. Therefore, the year's addition of even a scant 60,000,000 ounces to the silver holdings permitted some slight progress toward the goal set by the Silver Purchase Act that "one-fourth of the total monetary value of the gold and silver stocks shall be in silver." The proportion of silver at December 31, 1942, was 16 percent, an advance of % percent since December 31, 1941.

December 31, 1941.

Coinage.—Information from London indicates that the Royal Mint coined British Treasury silver acquired from the Indian Government, but the amount is unknown. Maria Theresa thalers, for export to Abyssinia, were minted, as well as some Colonial and domestic coinage. We are also advised that the Royal Mint of Canada purchased silver from that country's producers for current coinage purposes, and that the Bank of Mexico bought metal, part of which was to be minted for a South American country.

minted for a South American country.

According to an official statement, the amount of silver received at the United States mints during the first eleven months of 1942 for the purpose of foreign

<sup>&</sup>lt;sup>1</sup> For congressional acts with reference to coinage from April 2, 1792, to January 31, 1934, see Minerals Yearbook, 1937, p. 113; for gold prices in London, 1931-36, p. 114.

<sup>2</sup> For highest, lowest, and average price of silver in New York, 1874-1935, see Minerals Yearbook, 1937, p. 115; for ratio of silver to gold, 1687-1935, p. 121.

coinage manufacture was 8,991,000 fine ounces, some of which was bought outside of the United States. The identity of the countries obtaining this coinage was withheld.

A new high record for domestic silver coinage was made in 1942, the 11-month figure of 69,100,000 ounces being 16,900,000 ounces greater than the previous full year's record established in 1941. Of the total, 66,376,000 ounces were consumed in subsidiary coinage which excludes nickels and pennies, and 2,744,000 ounces were used in the new "silver" nickels. These latter coins contain 35 percent

silver, 56 percent copper, and 9 percent manganese.

Under legislation enacted toward the end of December, Secretary Morgenthau established specifications for a new, wartime 1-cent coin, of the same design as the present penny, but made of zino-coated steel. Minting of the new pennies will commence about February 1, 1943, and subsequently a 3-cent piece, also authorized under the recent law, may be put into circulation if the demand for

minor coins continues.

### CONSUMPTION AND USES

Gold.—The desirable properties and uses of gold in industry were described in considerable detail in the Gold and Silver chapter, Minerals Yearbook, 1941. In 1942 the war program called for substantially greater quantities of gold wire in instruments used in measuring the speeds of aircraft engines, gold-plated anodes for soundtransmitting apparatus, gold-alloy hair springs for use in highly accurate timepieces and marine chronometers, gold lining for special pieces of base-metal equipment used in chemical plants, gold-lined equipment for the artificial silk industry, and gold chloride for use in making colored film. Greater use of gold in the war program is necessarily restricted by the high price of the metal, and under present conditions it cannot hope to substitute in any great amount for critical base metals.

The second secon

Normally, 5 to 10 percent of the world output of gold is consumed by industry; the remaining 90 to 95 percent is used for monetary purposes. Industry in the United States in 1941 consumed approximately 2,000,000 ounces of gold, both old and new metal. amount was divided about as follows: Jewelry, 950,000 ounces; watch cases, 75,000 ounces; gold leaf, 60,000 ounces; electrical and industrial equipment, instruments, and medical and dental supplies, 915,000 ounces.3

Silver.—Consumption of industrial silver continued to mount rapidly in 1942, rising to an estimated gross amount of about 120,-500,000 ounces. Distribution by uses is estimated to have been as Distribution by uses is estimated to have been as follows:

SilverwarePhotographic goods	19, 600, 000	Solder	(1)
Jewelry Bearings	16, 500, 000 10, 600, 000	Chemical products, n. e. s_ Miscellaneous	(1) 21 300 000
Contacts	9, 300, 000 l	-	
Insignia Dental and medical	2, 200, 000	Total	120, 500, 000

1 Included elsewhere.

Greatest gains were in the use of silver for bearings, solders, brazing alloys, electrical contacts, photographic goods, insignia, and dental These uses are expected to require much and medical supplies. greater quantities of the metal in 1943 (except for insignia), but consumption of silver in jewlery and silverware will drop greatly.

<sup>3</sup> War Production Board, data as of May 14, 1943.

Nearly 60 percent of the silver consumed in the United States in 1942 probably went into war production; this proportion will be even greater in 1943. The large quantities used for solders and brazing alloys, electrical appliances, bearings, and other articles played a vital part in the production of virtually every airplane, tank, submarine, battleship, cargo ship, and field kitchen and in many kinds of instruments, guns, bombs, torpedoes, shells, and other weapons. Much silver was also used in highly important military photography, and smaller amounts for medical and dental work.

Much progress was made in utilizing the minimum 1,000,000,000 ounces (34,286 short tons) of "free" or nonconsumable silver loaned by the Treasury to the Defense Plant Corporation, under agreement of May 6, 1942, and allocated by the War Production Board. Late in 1942 the Board announced that all such silver either had been loaned to war industries or commitments had been made for its use, and by January 1943 some 22,000 tons had been shipped from the vaults. By far the greatest part of the metal went into bus bars for use in aluminum and magnesium plants, saving a substantial tonnage of copper.

The following table shows the net industrial consumption of gold and silver in the United States for the 10-year period 1933-42, inclusive, in terms of dollars for gold and fine ounces for silver. The quantity of each metal reclaimed and recovered from various sources is deducted from that issued for industrial use to give the net amount.

Net industrial consumption of gold and silver in the United States, 1933-421

		Gold (dollars)			Silver (fine ounces)		
Year  1933 1934 1935 1936 1937 1938 1940 1941 1941	Returned from indus- trial use  22, 805, 960 75, 927, 285 58, 390, 675 36, 875, 770 36, 407, 945 30, 480, 835 31, 328, 360 27, 872, 355 30, 975, 490 38, 447, 685	Issued for industrial use  17, 013, 260 14, 232, 795 25, 929, 497 32, 967, 937 39, 622, 338 30, 156, 754 38, 788, 960 41, 178, 387 67, 977, 110 75, 742, 495	Net industrial consumption  -5, 792, 700 -61, 694, 490 -32, 461, 178 -2, 907, 833 3, 214, 393 -324, 081 7, 460, 600 13, 306, 032 37, 001, 620 47, 294, 810	Returned from indus- trial use 18, 532, 880 28, 186, 178 35, 903, 107 16, 703, 353 23, 564, 986 18, 438, 947 24, 972, 260 22, 563, 729 20, 361, 256	Issued for industrial use  29, 343, 451 39, 678, 603 41, 192, 023 35, 842, 674 51, 292, 770 38, 620, 473 69, 585, 256 67, 062, 682 92, 793, 574 311, 419, 224	Net industrial consumption  10, 810, 571 11, 492, 425 5, 288, 916 19, 139, 321 27, 727, 234 20, 181, 626 44, 613, 626 44, 613, 626 44, 613, 686 101, 398, 695	

<sup>1</sup> U.S. Bureau of the Mint.

# IMPORTS AND EXPORTS 4

Value of gold and silver imported into and exported from the United States, 1941-42, by classes

	Imports	Exports	Excess of imports over exports
Gold: Contained in ore and base bullion Bullion refined United States coin Foreign coin	\$103, 492, 789 877, 321, 316 728 1, 627, 194	\$37,004 19,162 8,114	\$103, 455, 785 877, 302, 154 17, 386 1, 627, 194
<sup>1</sup> Excess of exports.	982, 442, 027	64, 280	982, 377, 747

<sup>4</sup> Figures compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce. 556250—43——7

West of the second seco

Value of gold and silver imported into and exported from the United States, 1941-42, by classes—Continued

	Imports	Exports	Excess of imports over exports
1941—Continued			
Silver: Contained in ore and base bullion Bullion refined U nited States coin Foreign coin	\$17,605,811 29,256,903 188,996 1,703	\$1, 401 2, 957, 847 176, 000 2, 538, 113	\$17, 604, 410 26, 299, 056 12, 996 1 2, 536, 410
	47, 053, 413	5, 673, 361	41, 380, 052
Gold: Contained in ore and base bullion	47, 413, 550	22, 685	47, 390, 865
Bullion refined	268, 005, 947 290 359, 929	79, 441	267, 926, 506 290 359, 929
물통하다 항공하는 전문에 걸어 하는 경기를 하다.	315, 779, 716	102, 126	315, 677, 590
Silver: Contained in ore and base bullion Bullion refined United States coin Foreign coin	12, 711, 949 28, 002, 573 163, 085 225, 542	1, 635 504, 105 26, 000 1, 467, 750	12,710,314 27,498,468 137,085 11,242,208
	41, 103, 149	1,999,490	39, 103, 659

The second secon

<sup>1</sup> Excess of exports.




FIGURE 1.—Gold and silver imports and exports, with net movements, 1900-1942.

# DOMESTIC SUPPLY

The following tables show the sources of domestic supply of gold It is noted that during this period and silver, by percent, for 1936-42. dry and siliceous ores and placer gravels supplied 86 to 90 percent of total United States gold production, exclusive of the Philippine Islands and Puerto Rico; base-metal ores supplied the remaining 10 to 14 On the whole, placers have increased in relative importance in gold production since 1928, and dry and siliceous ores have steadily decreased in relative importance since 1932.

In the production of silver dry and siliceous ores are less important than in the production of gold, and placers are almost of no consequence. In only 1 year during the past 20 years (1938) have dry and siliceous ores supplied as much as half of the total United States out-The low point was reached in 1928, when these ores put of silver.

supplied only 19 percent, and base-metal ores 81 percent.

Mine production of gold in the United States, 1936-42, by percent from sources, and in total fine ounces 12

Year	Placers	Dry and siliceous ore	Copper ore	Lead ore	Zinc ore	Zinc-lead, zinc-copper, lead-copper, and zinc- lead-copper ores	ounces
1936 1937 1938 1939 1940 1941 1942	23. 9 24. 6 27. 9 28. 6 31. 0 31. 3 29. 3	64. 0 60. 8 62. 1 59. 8 55. 6 54. 3 50. 0	10. 0 12. 0 8. 0 10. 1 11. 0 11. 8 17. 0	0.5 .6 .4 .3 .4 .5	(3) (3) (3) (3) (3)	1.6 1.9 1.6 1.3 2.0 2.0 2.9	3, 782, 669 4, 117, 078 4, 267, 469 4, 673, 042 4, 869, 949 4, 750, 865 3, 457, 110

Philippine Islands and Puerto Rico excluded.
 1922-35 data are shown on p. 132, Minerals Yearbook, 1937, Review of 1936.
 Less than 0.1 percent.

Mine production of silver in the United States, 1936-42, by percent from sources, and in total fine ounces 12

		Percent from						
Year	Placers	Dry and siliceous ore	Copper	Lead ore	Zinc ore	Zinc-lead, zinc-copper, lead-copper, and zinc- lead-copper ores		
1936 1937 1938 1939 1940 1941	0.2233333333333333333333333333333333333	43. 0 45. 0 51. 6 47. 0 41. 3 41. 2 37. 3	28. 5 28. 5 25. 8 28. 6 29. 3 27. 9 27. 8	6. 2 6. 7 5. 5 4. 6 4. 5 5. 6 5. 5	(3) 0.8 (4) .1 (7) .3 1.2	22. 2 18. 9 17. 0 19. 4 24. 6 24. 7 28. 0	61, 152, 534 71, 408, 625 61, 705, 837 64, 373, 281 70, 549, 362 67, 258, 997 54, 090, 765	

Philippine Islands and Puerto Rico excluded.
 1922-35 data are shown on p. 134, Minerals Yearbook, 1937, Review of 1936.
 Less than 0.1 percent.

## MINE REPORT

### METHOD OF COLLECTING STATISTICS

The second table in this report presents the official refinery figures for production of gold and silver in the United States from 1938 to 1942, as agreed upon by the Bureau of the Mint and the Bureau of Mines. These figures record the output of gold and silver bullion from domestic ore in marketable form as metals, either refined or unrefined.

To trace the gold and silver produced back to its source by States, counties, and mining districts, the Bureau of Mines systematically investigates the "mine production" of ores containing gold and silver and the output of the placer mines, the total being classified by methods of production and by kinds of ore, as well as by mining districts. The resulting figures form the basis of the mine reports.

Of the two systems for ascertaining the production of gold and silver, one is a measure of the metallurgic industry and the other of the mining industry; one reports the metal actually recovered in marketable form and the other the mine output and its recoverable content. The two methods will not produce identical results, but data for a period of years long enough to compensate for overlap or lag should agree within allowable limits of error.

Compared with the mine reports, the mint reports for the 38 years show a total excess of gold of 297,374 ounces (a difference of 0.21 percent) and a total excess of silver of 12,848,477 ounces (a difference of 0.58 percent).

Gold and silver produced in the United States, 1905-42, in fine ounces, according to mint and mine returns, in terms of recovered metals

	M	<b>l</b> int	Mine		
Year	Gold	Silver	Gold	Silver	
1905-37 1938 1939 1940 1941	114, 224, 734 5, 089, 811 5, 611, 171 6, 003, 105 5, 976, 419 3, 741, 806	1, 898, 028, 783 62, 665, 335 65, 119, 513 69, 585, 734 72, 336, 029 56, 090, 855 2, 223, 826, 249	114, 024, 647 5, 170, 743 5, 672, 485 5, 984, 163 5, 881, 798 3, 615, 836	1, 887, 909, 257 62, 873, 450 65, 565, 024 71, 824, 746 68, 483, 333 54, 321, 962 2, 210, 977, 772	

### UNITS OF MEASUREMENTS

All tonnage figures are short tons of 2,000 pounds "dry weight"; that is, they do not include moisture. The weight unit for gold and silver is the troy ounce (480 grains). The totals are calculated upon the basis of recovered and recoverable fine gold and silver shown by assays to be contained in ore, bullion, and other material produced. Prices of gold and silver are discussed in a preceding section of this report.

# MINES PRODUCING

#### LEADING GOLD PRODUCERS

The output of the 29 largest gold producers in the United States (Philippine Islands and Puerto Rico excluded) in 1942, none of which produced less than 17,000 ounces, was 2,086,084 fine ounces (60 percent

of the total). Six of the companies working placer mines (five with floating connected-bucket dredges and one with a dragline dredge) recovered 421,818 ounces of gold; the rest of the output of the largest producers came from lode mines. The total output of lode mines and placers producing less than 17,000 ounces each was 1,371,026 ounces.

Largest producers of gold in the United States in 1942, in order of output 1

Rank	Operator	State	Mining district	Source of gold
1	Homestake Mining Co	South Dakota.	Whitewood	Dry and siliceous gold
2 3	Utah Copper Co- United States Smelting, Re-	Utah Alaska	West Mountain Fairbanks and Nome	ore. Copper ore. Dredging gravel.
4	fining & Mining Co. Phelps Dodge Corporation	Arizona	Ajo, Copper Mountain, Verde, Warren.	Copper ore, dry and siliceous gold ore, dry
5	Golden Cycle Corporation 2	Colorado	Cripple Creek, etc	and siliceous silver ore Dry and siliceous gold
6	Yuba Consolidated Gold Fields.	California	Callahan, Oroville, Yuba River.	ore. Dredging gravel.
7	Alaska Juneau Gold Mining	Alaska	Juneau	Dry and siliceous gold ore.
8 9	Natomas Co. Empire Star Mines Co., Ltd.	Californiado	Folsom Browns Valley, Grass Valley-Nevada City.	Dredging gravel. Dry and siliceous ore.
10	Idaho Maryland Mines Corporation.	do	Grass Valley-Nevada City.	Do.
11 12	Howe Sound Co	Nevada	Chelan Lake Potosi	Copper ore. Dry and siliceous ore.
13	Nevada Consolidated Copper Corporation.	do		Copper ore.
14	Lava Cap Gold Mining Corporation.	California	City	Dry and siliceous ore.
15	Consolidated Coppermines Corporation.	Nevada	Robinson	Copper ore.
16	United States Smelting, Refining & Mining Co.	Utah	West Mountain	dry and siliceous gold-
17	Alaska-Pacific Consolidated Mining Co.	Alaska	Willow Creek	silver ore.  Dry and siliceous gold  ore.
18	Mammoth-St. Anthony, Ltd	Arizona	Old Hat	Zinc-lead ore, dry and siliceous gold ore.
19	Manhattan Gold Dredging	Nevada	Manhattan	Dredging gravel.
20	Talache Mines, Inc	Idaho	Middle Boise	Dry and siliceous gold
21 22	Capital Dredging CoBald Mountain Mining Co	California South Dakota.	Folsom Trojan	Dredging gravel.  Dry and siliceous gold ore.
23 24	Dayton Dredging Co	Nevada Arizona	Silver CitySan Francisco	Dredging gravel. Dry and siliceous gold ore.
25 26	Golden Queen Mining Co Telluride Mines, Inc	California Colorado	Mojave Upper San Miguel	Dry and siliceous ore. Dry and siliceous gold- silver ore.
27	Knob Hill Mines, Inc	Washington	Republic	Dry and siliceous gold
28	Anaconda Copper Mining Co.	Montana	Summit Valley or Butte.	ore. Copper ore, zinc-lead ore, dry and siliceous
29	Cactus Mines Co	California	Mojave	silver ore. Dry and siliceous ore.

<sup>&</sup>lt;sup>1</sup> Philippine Islands excluded.

<sup>2</sup> Custom mill. Includes mainly ore from Cresson, Portland, Ajax, Vindicator, and other mines in Cripple Creek district, Colorado, but also from other districts in Colorado.

### LEADING SILVER PRODUCERS

The output of silver from the 48 leading silver-producing companies in 1942, none of which produced less than 180,000 ounces, was 43,426,353 ounces—80 percent of the total mine output of the United States (Philippine Islands and Puerto Rico excluded); the remaining 10,523,543 ounces (placer production excluded) came from about 2,600 lode mines, many of which derive a substantial net income from the silver content.

# Largest producers of silver in the United States in 1942, in order of output

Rank	Operator	State	Mining district	Source of silver
1	Anaconda Copper Mining Co.	Montana	Summit Valley or Butte.	Copper ore, zonc-lead ore, dry and siliceous
2	Sunshine Mining Co	Idaho	Evolution	silver ore. Dry and siliceous silver ore.
3	Phelps Dodge Corporation	Arizona	Ajo, Copper Moun- tain, Verde, War- ren.	Copper ore, dry and siliceous gold ore, dry and siliceous silver ore.
<b>4</b> 5	Utah Copper Co- United States Smelting, Re- fining & Mining Co.	Utahdo	West Mountain Ophir and West Mountain.	Copper ore. Zinc-lead-copper ore, zinc-lead ore, lead ore, dry and siliceous gold- silver ore.
6	Bunker Hill & Sullivan Mining & Concentrating Co.	Idaho	Yreka	Zinc-lead ore, lead ore, dry and siliceous silver ore.
7	Coeur d'Alene Mines Corporation.	do	Evolution	Dry and siliceous silver
8	Tintic Standard Mining Co	Utah		Lead ore, dry and sili- ceous gold-silver ore, dry and siliceous silver ore.
9	Federal Mining & Smelting Co.	Idaho		Zinc-lead ore.
10 11	Hecla Mining Co Silver King Coalition Mines Co.	Utah	Uintah	Zinc-lead ore, lead ore. Do.
12	Emperius Mining Co.1	Colorado		Dry and siliceous silver ore.
13 14	Polaris Mining Co. Anaconda Copper Mining Co. (Flathead and West Flathead mines).	Idaho Montana	Evolution Hog Heaven	Do. Lead ore, dry and sili- ceous silver ore.
15	American Metal Co. (Presidio mine).	Texas	Shafter	Dry and siliceous silver ore.
16 17	Desert Silver, Inc Triumph Mining Co	Nevada Idaho	Silver Peak	Dry and siliceous ore. Zinc-lead ore.
18 19	Mines Co.  New Park Mining Co.	Utahdo	Blue Ledge	Do. Do.
20 21	Magma Copper Co Shattuck-Denn Mining Cor- poration.	Arizonadodo	Pioneer Big Bug and Warren	Copper ore, zinc ore. Copper ore, zinc-lead ore, dry and siliceous gold silver ore
22 23	Sherman Lead Co	Idaho Montana	Lelande Flint Creek	Dry and siliceous gold ore, dry and siliceous silver ore.
24	Lexington Mining Co			Lead ore, dry and sili- ceous silver ore.
25 26	New Jersey Zinc Co., Empire Zinc Division. Anaconda Copper Mining Co.	Colorado Montana		Zinc-lead ore, dry and siliceous silver ore. Zinc-lead ore.
27	Anaconda Copper Mining Co. (Emma and Ophir). Cactus Mines Co	California Utah	Butte.	Dry and siliceous ore.
28 29	Park Utah Consolidated Mines Co. American Smelting & Refin-	Arizona	-	Zinc-lead ore, lead ore.
	ing Co. (Trench and Flux Unit).			Zinc-lead ore.
30	Chief Consolidated Mining Co.	Utah		dry and siliceous gold- silver ore.
31 32	Shenandoah-Dives Mining Co- Lessees of the Tonopah Min- ing Co. of Nevada.	Colorado Nevada	Animas Tonopah	Zinc-lead ore. Dry and siliceous ore.
33	Midnight Mining Co	Colorado	Roaring Fork	Dry and siliceous silver ore.
34	Lava Cap Gold Mining Corporation.	California	Grass Valley-Nevada City.	Dry and siliceous ore.
35 36 37	Bristol Silver Mines Co Sullivan Mining Co Combined Metals Reduction	Nevada Idaho Utah	Jack Rabbit Hunter	Copper ore. Zinc-lead ore. Zinc-lead ore, lead ore.
38	Co. (West Calumet mine). St. Joseph Lead Co	Montana	Barker	Zinc-lead ore.

<sup>&</sup>lt;sup>1</sup> Comprises output from all the Creede district including custom ore from sublessees.

Largest producers of silver in the United States in 1942, in order of output-Continued

Rank	Operator	State	Mining district	Source of silver
39 40 41	Shoshone Mines, Inc	California Utah	Resting Springs West Mountain Carson or French	Lead ore. Zinc-lead ore, dry and siliceous gold ore.
42 43	tion. Telluride Mines, Inc. Combined Metals Reduction	Colorado Nevada	Carson or French Creek. Upper San Miguel Pioche	Dry and siliceous gold- silver ore. Do. Zine-lead ore.
44	Mike Horse Mining & Milling	Montana	Heddleston	Do.
45	Blackhawk Consolidated Mines Co.	New Mexico	Mogollon	Dry and siliceous gold- silver ore.
46 47	Golden Queen Mining Co Tamarack & Custer Consoli- dated Mining Co.	California Idaho	Mojave Placer Center	Dry and siliceous ore. Zinc-lead ore.
48	Dayrock Mining Co	do	do	Lead ore.

#### NUMBER OF MINES

The following table indicates the number of mines that produced gold and silver in 1941 and 1942. The placers are those in which gold and silver in natural alloy and, in a few placers, platinum are recovered from gravel and sand, whether by hand washing, sluicing, hydraulicking, drifting (in frozen ground or ancient buried river channels), or dredging. The lode mines are those yielding gold and silver from ore as distinguished from gravel, mainly from underground workings, and include those that yield ore mined chiefly for copper, lead, or zinc but that contribute the precious metals as byproducts. In addition to the producing mines enumerated here many properties were being prospected and developed, and many other mining claims were being held by assessment work only.

The enumeration of placer mines is less satisfactory than that of lode mines, because some are operated only temporarily and are individually small. As far as possible the unit, as for lode mines, is

not the operator but the mining claim or group of claims.

Number of mines in the United States producing gold and silver, 1941-42, by States

State	Lo	de	Pla	ocer	Total		
	1941	1942	1941	1942	1941	1942	
Alabama	2	1			2	1	
Alaska	56	38	799	453	855 989	491	
Arizona		503	184	163	989	666	
California		434	724	428	1, 559	862	
Colorado	579	311	324	68	903	379	
Georgia	7	3	11	15	18	18	
Idaho	329	201	524	236	853	437	
Illinois	4	. 2			300	. 201	
Michigan	l īl	5			71	2	
Missouri	3	3			3	3	
Montana	612	369	325	170	937	539	
Nevada	799	434	78	49	877		
New Mexico	145	78	103	48	248	483	
New York	140	10	103	948	298	126	
North Carolina	5	7	2		#		
Oregon		48		1	2,7	8	
Pennsylvania	21	. 40	153	83	244	131	
South Carolina		+			1	1	
South Delecte	16	. 4			.7	4	
South Dakota	10	5	41	13	51	18	
Tennessee	4	3			4	3	
TexasUtah	9	. 7			9	· 7	
	167	119	12	6	179	125	
Virginia	1	2	1 1	1	2	3	
Washington	61	37	56	18	117	55	
Wyoming	8	6	12	6	20	12	
• •	4, 542	2, 619	3, 349	1,758	7, 891	4, 377	

### MINE PRODUCTION

### SUMMARY

The following table gives the mine production of gold and silver in 1941 and 1942, by States, in terms of recovered metals, as calculated by the Bureau of Mines from reports from the producing mines. The annual percentage gains in gold production in the years following the 69-percent increase in the price of gold are as follows: 1934 over 1933, 19 percent; 1935 over 1934, 18 percent; 1936 over 1935, 19 percent; 1937 over 1936, 9 percent; 1938 over 1937, 7 percent; 1939 over 1938, 10 percent; 1940 over 1939, 5 percent; but 1941 decreased from 1940, 2 percent; and 1942 decreased from 1941, 27 percent. The total gain in 1940 over 1933 was 128 percent. The output of silver decreased 20 percent in 1942 from 1941 but was 133 percent above that in 1933.

Mine production of gold and silver in the United States, 1941-42, by regions and States, in terms of recovered metals 1

	-		Gold					Silver		
Region and State	Fine ounces		Increase or decrease	Value (at \$35 per ounce)		Fine ounces		Increase or decrease	Value (at \$0.71111+ per ounce)	
	1941	1942	(percent)	1941	1942	1941	1942	(percent)	1941	1942
Western States and Alaska:										Twee Control
Alaska	694, 467	487, 621	-30	\$24, 341, 345	\$17, 066, 735	191, 522	119, 704	-37	\$136, 193	\$85, 12
Arizona	315, 392	253, 651	-20	11, 038, 720	8, 877, 785 29, 679, 895	7, 498, 260	7, 064, 467	-6	5, 332, 096	5, 023, 6
California	1, 408, 793	847, 997	-40 l	49, 307, 755	20 670 805	2 154 188	1, 450, 440	-33	1, 531, 867	1, 031, 4
Colorado	380 020	268, 627	-29	13, 301, 015	0,401,045	2, 154, 188 7, 301, 697	3, 096, 211	-58	5, 192, 318	0 001 7
Idaho	149, 816	95, 020	-37	5, 243, 560	0, 101, 310	1,001,001	3,090,211		0, 192, 518	2, 201, 7 10, 414, 1
Montana	140,010	146, 892		0, 240, 000	3, 320, 700	16, 672, 410	14, 644, 890	-12	11, 855, 936	10, 414, 1
Morrado	246, 475		-40	8, 626, 625	9, 401, 945 3, 325, 700 5, 141, 220 10, 328, 920	12, 386, 925	11, 188, 118 3, 723, 435	-10	8, 808, 480	7, 955, 9 2, 647, 7
Nevada	366, 403	295, 112	-19	12, 824, 105	10, 328, 920	5, 830, 238	3, 723, 435	-36	4, 145, 947	2, 647, 7
New Mexico	27, 845	11, 961	-57	974, 575	418, 635	1, 328, 317	676, 170	-49	944, 581	480.8
Oregon South Dakota	96, 565	46, 233 522, 098	-52	3, 379, 775	1, 618, 155	276, 158	87, 376	-68	196, 379	62, 1
South Dakota	600, 637	522, 098	-13	21, 022, 295	18, 273, 430	170, 771	186, 937	l +ŏ	121, 437	132, 9
Texas	1 306	236	-23	10,710	8, 260	1,096,027	672, 781	-39	779, 397	478, 4
Utah	356, 501	391, 544	+10	12, 477, 535	13, 704, 040	11, 395, 485	10, 574, 955	-30 -7	8, 103, 456	7, 519, 9
Washington	84, 176	75, 396	-10 -10	2, 946, 160	2, 638, 860	11, 000, 400			8, 103, 400	7, 519, 9
Wyoming	478	23	-10 -95	2, 940, 100	2, 000, 800	402, 030	369, 038	-8	285, 888	262, 4
W yoming	4/0	20	-90	16, 730	805	94	52	-45	67	8
	4, 728, 883	3, 442, 411	-27	165, 510, 905	120, 484, 385	66, 704, 122	53, 854, 574	-19	47, 434, 042	38, 296, 58
Eastern States:										
Alabama	30		-97	1,050		3				
Convoio	311	1			35			✓ <b>—100</b>	2	
Georgia	311	. 30	-90	10, 885	1,050	38	7	-82	27	
New York						37, 734	40,012	+6	26, 833	28, 4
North Carolina	3, 244	4,077	+26	113, 540	142, 695	7, 439	8, 259	+11	5, 290	5, 8'
Pennsylvania South Carolina	2, 422	2, 499	+3	84, 770	87, 465	15, 016	15, 501	+3	10, 678	11,0
South Carolina	15, 508	7,824	-50	542, 780	273, 840	6, 525	5,064	-22	4, 640	3, 6
Tennessee	227	159	-30	7, 945	5, 565	39, 161	34, 671	-11	27, 848	0,0
Virginia.	240	109	-55	8, 400			34, 071			24, 6
, weare	240	109	-00	8, 400	3, 815	135	1, 793	+1,228	96	1, 2
	21, 982	14, 699	-33	769, 370	514, 465	106, 051	105, 307	-i	75, 414	74, 88
Central States:										
Illinois						20, 340	104		14 404	
Michigan								-99	14, 464	40.0
Missouri						60, 796	61, 674	+1	43, 233	43, 8
ATANDOULI						367, 688	69, 106	-81	261, 467	49, 14
						448, 824	130, 884	-71	319, 164	93, 07
	4 750 005	2 457 110	07	144 000 075	100 000 070					
	4, 750, 865	3, 457, 110	-27	166, 280, 275	120, 998, 850	67, 258, 997	54, 090, 765	-20	47, 828, 620	38, 464, 54

<sup>1</sup> Philippine Islands and Puerto Rico excluded.

Ore produced in the United States and average recovery in fine ounces of gold and silver per ton in 1942 1

	Go	ld ore		Gold-silver ore			Silv	er ore	
State	Short tons	ounc	erage es per	Short			Short tons	oun	erage es per on
		Gold	Silver		Gold	Silver		Gold	Silver
Western States: Arizona. California. Colorado. Idaho. Montana. Nevada. New Mexico. Oregon. South Dakota. Texas. Utah. Washington Wyoming. Total, Western States. Alaska.	29, 055 1, 454, 387 126, 405 93, 957 59 6, 566, 065 2, 815, 287	498, 879 0. 168 0. 25 124, 668 0. 078 3. 04 34, 395 (2, 062, 599 183 .49 621 .271 13. 84 13, 331 932, 145 .202 .31 192, 709 .130 2. 07 88, 132 142, 952 .248 .91 173, 389 .043 2. 07 458, 533 322, 140 .215 .51 .77, 231 .106 6. 34 134, 153 897, 769 .152 .29 337, 974 .078 3. 66 81, 667 5, 718 .202 .77 29, 997 .137 8. 91 2, 116 29, 055 .260 .81 1, 580 .083 10. 97 1, 035 1, 454, 387 359 .12	0. 030 . 021, . 027 . 001 . 025 . 037 . 054 . 195 . 037 . 042 . 037	12. 22 5. 22 16. 2 16. 4 11. 7 11. 2 20. 5 38. 1 6. 6 11. 5					
Eastern States				1 163 070	083	3 47	008 893	014	13 70
Eastern States	9, 487, 907	.174	.26	1, 163, 970	.083	3. 47	996, 823	. 014	13, 70
Eastern States	9, 487, 907	. 174 per ore			ad ore			opper o	
State  Western States: Arizona. California. Colorado. Idaho. Montana. Nevada. New Mexico. Oregon. South Dakota. Texas.	9, 487, 907  Cop  Short tons  1 32, 856, 971	Av ound t Gold	. 26 erage es per con Silver 0. 15 . 18 15 . 33 12 . 39 1 . 43 . 07 . 02 . 29 4 . 13	Short tons  25, 898 29, 857 6, 418 313, 317 15, 936 32, 081 694	Gold  0. 084 .165 .226 .001 .149 .045 .209	erage erage per con Silver 3. 92 8. 31 9. 62 3. 52 11. 37 13. 54 5. 26	Lead-c Short tons  473 5 22 83 7 618	Av ound	erage ess per on Silver 5.00 60.22 22.4 148.8 6.25.77
State  Western States: Arizona. California. Colorado. Idaho. Montana. New Mexico. Oregon. South Dakota. Texas. Utah. Washington. Wyoming. Total. Western	9, 487, 907  Cop  Short tons  1 32, 856, 971 393, 944 7, 904, 443 7, 631, 752 506 33, 611, 061 717, 124	Av ounce to the control of the contr	. 26 erage res per con Silver  0. 15 . 18 . 15 . 33 . 12 . 39 . 1. 43 07	25, 898 29, 857 6, 418 313, 317 15, 936 32, 081 694 75, 758 161 25	Gold  0.084 .165 .226 .001 .149 .045 .209	erage res per con Silver  3. 92 8. 31 9. 62 11. 35 12. 13 10. 38 4. 42 2. 04	Lead-c Short tons  473 5 22 83 7 618	Gold  0.032 .600 1.091	silver  5.00 60.20 22.4 148.8 6.22 5.77
State  Western States: Arizona California Colorado Idaho Montana Nevada Nevada Nevada Oregon South Dakota Texas Utah Washington Wyoming	9, 487, 907  Copy Short tons  1 32, 856, 971 393, 944 2, 210 4, 338, 714 7, 904, 443 7, 631, 752 506 33, 611, 061 717, 124	. 174  Der ore  Av ound t  Gold  0. 004 . 001 . 212 . 069 . 004 . 010 . 001 . 034 . 002 . 009	. 26 erage res per ron Silver  0. 15 . 18 . 15 . 33 . 12 . 39 . 1 . 43 . 02 29 4. 13 . 08 . 08	25, 898 29, 857 6, 418 313, 317 15, 936 32, 081 694	Gold  0. 084 .165 .226 .001 .149 .045 .209	erage res per con Silver 3. 92 8. 31 9. 62 3. 52 11. 37 13. 54 5. 26	Lead-c Short tons  473 5 22 83 7 618	Av ound t Gold 0.032 .600 1.091	erage es per on

See footnotes at end of table.

一般のでは、一般のでは、少さの歌のは最後の歌奏という、多なないのである。 いかい

# Ore produced in the United States and average recovery in fine ounces of gold and silver per ton in 1942 1—Continued

	Zi	nc ore		Zinc-lead and zi		-copper, l-copper	Total ore			
State	Short tons	A verage ounces per ton		Shorttons	A verage ounces per ton		Short tons	Average ounces per ton		
		Gold	Silver		Gold	Silver		Gold	Silver	
Western States: Arizona. California. Colorado. Idaho. Montana Nevada. New Mexico. Oregon. South Dakota Texas. Utah. Washington. Wyoming.	106, 400 2, 089 590 20, 561 4218, 235 47, 522 330, 239	0. 011 .004 .010 .011 .011 .001	1. 87 1. 10 4. 26 6. 21 .30 1. 84 .44	273, 047 752 577, 162 1, 789, 659 571, 871 8i, 916 220, 378 9, 997	0. 031 . 007 . 049 . 004 . 012 . 011 . 001 . 017	3. 09 2. 05 1. 56 2. 99 4. 36 2. 50 2. 24 . 75 6. 18 . 06	2 33, 920, 731 2, 503, 198 1, 797, 386 2, 900, 704 4 5, 678, 280 9, 383, 379 8, 221, 512 31, 728 1, 464, 384 1, 981, 655 7 1, 222, 937 84	0.007 .153 .137 .017 .019 .026 .001 .249 .357 .002 .011 .061	0. 21 . 56 1. 72 5. 05 1. 97 . 39 . 08 2. 53 . 13 6. 68 . 30 . 30	
Total, West- ern States Alaska	742, 346	.003	.85	4, 780, 323	. 021	3. 16	102, 206, 676 2, 816, 668	. 022	. 52	
Eastern States	2, 364, 229			846, 820	(5)	. 05	8 4. 166, 226	.004	.02	
	3, 106, 575	. 001	. 20	5, 627, 143	.018	2. 69	109, 189, 570	. 022	. 49	

# Gold and silver, produced in the Western States of the United States, 1848-1942, and in Alaska, 1880-1942, in terms of recovered metals

[Original research, 1848-1903, by Chas. W. Henderson; 1904-42, by western offices, Economics and Statistics Service]

State	Period	Gold		Silver	
		Fine ounces	Value	Fine ounces	Value
Alaska Arizona California Colorado Idaho Montana Nevada Nevada Oregon South Dakota Texas Utah Washington Wyoming	1880-1942 1880-1942 1848-1942 1858-1942 1863-1942 1862-1942 1859-1942 1859-1942 1856-1942 1876-1942 1884-1942 1864-1942 1860-1942	25, 639, 651 10, 427, 940 101, 110, 756 38, 565, 382 7, 724, 178 16, 827, 410 25, 070, 558 2, 160, 741 5, 667, 021 20, 560, 041 8, 277 9, 449, 773 1, 957, 121 77, 914	\$610, 402, 387 262, 473, 055 2, 240, 980, 112, 843, 665, 334 173, 485, 633 373, 412, 562 556, 031, 206 48, 960, 128 126, 308, 778 501, 198, 644 230, 967, 095 47, 254, 558 1, 835, 318	19, 682, 372 275, 752, 505 104, 482, 628 721, 046, 775 484, 219, 847 724, 391, 028 584, 429, 765 65, 952, 746 5, 177, 158 9, 533, 213 33, 186, 537 691, 875, 106 11, 591, 928 74, 632	\$14,000,794 204,905,390 84,367,327 560,682,926 332,614,231 529,152,66,926,177 51,631,038 4,759,521 6,781,561 23,362,715 504,275,236 8,203,574 51,752
Total, Western States and Alaska	1848-1942	265, 246, 763	6, 007, 198, 450	3, 731, 396, 240	2, 861, 704, 909

<sup>1</sup> Illinois, Michigan, Missouri, Philippine Islands, and Puerto Rico excluded.
2 Includes 4,199,268 tons of copper ore leached from which no gold or silver was recovered.
3 Includes zinc-copper ore from Arizona and zinc-lead-copper ore from Utah.
4 Includes 204,362 tons of current slag fumed which contained no gold.
5 Less than 0.0005 ounce per ton.
6 Includes 87,831 tons of zinc-lead slag.
7 Excludes 180,000 tons of current tailings from copper ore cyanided, not included in total ore treated in tate. State.

8 Excludes magnetite-pyrite-chalcopyrite ore from Pennsylvania.

ORE PRODUCTION, CLASSIFICATION, METAL YIELD, AND METHODS OF RECOVERY

The best index of lode mining is the quantity and metallic content of ore mined rather than the number of mines or operators. The following tables give details of classes of ore, metal yield in fine ounces of gold and silver to the ton, and gold and silver output by classes of ore and by methods of recovery, embracing all ores that produced gold and silver in the United States (excluding the Philippine Islands and Puerto Rico) in 1942. The individual State chapters from which these tables were compiled contain additional tables and text on the

subject and may be found elsewhere in this volume.

The classification originally adopted in 1905 on the basis of smelter terminology, smelter settlement contracts, and smelter recovery has been used continuously in succeeding years, except for modifications necessitated by the improvement in recovery of metals and the lowering of grade of complex ores treated, accomplished by improved mill concentration processes. A "dry" ore is one that carries so little lead or copper that by itself in quantity it would not satisfy the requirements for the smelter charge in lead smelting or copper smelting, The copper ores include those smelting ores that conrespectively. tain 2.5 percent dry assay or more of copper (or less than this percentage if no other metal is present), or those ores concentrated chiefly for their copper content. The lead ores are those that contain 5 percent dry assay (minimum lead smelting charge requires 7.5 to 8.5 percent wet assay) or more of lead, irrespective of precious-metal content; an ore that carries any grade of lead exclusively is called a lead ore. Zinc smelting ores (chiefly oxides) range from 16 to 45 percent zinc; zinc concentrating ores include any grade of zinc ore that makes marketable zinc concentrate, irrespective of precious-metal The mixed ores are combinations of those enumerated. smelter classification applies to concentrates.

The second s

Siliceous (silica<sup>5</sup> in excess of iron) gold, gold-silver, and silver ores containing too little copper, lead, or zinc to be classified as copper, lead, zinc, or mixed ores are called "dry" ores regardless of the ratio of concentration, except low-grade ore milled chiefly for its copper content and having very little or no precious-metal content (chiefly the "porphyry coppers") and ores from which separate products of lead concentrates and zinc concentrates are made. The crude ore into the mill in these two exceptional instances thus takes its name from its products—a name that is also justified by the mineralogical content and final recovery of metals. The "dry and siliceous ores" thus, by elimination, include both dry siliceous and irony, but chiefly siliceous, ores valuable for their gold and silver content, regardless of method of treatment, and dry fluxing ores carrying considerable quantities of iron and manganese oxides, or iron sulfide, and very small quantities of gold and silver. Dry and siliceous gold ores are those that by inspection are overwhelmingly of gold content; a similar qualification applies to silver ores; decision as to "gold-silver" ore is made arbitrarily on a basis of value, using the rule that the metal of lower value is not used in the bimetal classification unless its value is equal to or over one-quarter of the combined value of gold and silver.

The lead, zinc, and zinc-lead ores in most districts in the Eastern

<sup>&</sup>lt;sup>5</sup> Except where mineralization approaches a matte, ores in their natural state generally contain more silica than iron and usually are highly siliceous.

and Central States carry no appreciable quantity of gold or silver; such ores are excluded from this report unless otherwise indicated.

Mine production of gold in the United States in 1942, by States and sources, in fine ounces, in terms of recovered metals 1

State	Placers	Dry and siliceous ore	Copper	Lead ore	Lead- copper ore	Zine ore	Zinc-lead, zinc- copper, and zinc-lead, copper ores <sup>2</sup>	Total
Alabama		- 1						
Alaska	350, 122	137, 499						107.001
Arizona	2,836	94, 310	144, 764	2, 174	15	1, 152	8,400	487, 621 253, 651
California	464, 926	377, 702	436	4, 916	3	1, 102	5, 400	847, 997
Colorado	22, 617	216, 166	44	1, 451	24	6	28, 319	268, 627
Georgia	15	15					20,010	200, 027
Idaho	44, 580	43, 277	153	313		222	6, 475	95,020
Montana	41, 242	80, 993	15, 261	2, 368		101	6, 927	146, 892
Nevada New Mexico	47, 354	166, 302	78, 548	1, 432		537	939	295, 112
North Carolina	1,247	5, 381	4,815	145	4	238	131	11,961
Oregon	100 000	3,975	101					4,077
Pennsylvania	38, 336	7, 895	2					46, 233
South Carolina		7 004	<sup>8</sup> 2, 499					<sup>3</sup> 2, 499 7, 824
South Dakota	33	7,824						7,824
Tennessee	90	521, 900	150				165	522, 098
Texas		235	159					159
Utah	32	39, 580	291, 806	9, 727		6	FO 200	236
Virginia	53	46	201,000	0,121		0	50, 393	391, 544
Washington	356	26, 524	48, 399				10	109
Wyoming	12	11					117	75, 396 23
	1, 013, 762	1, 729, 636	586, 988	22, 526	46	2, 271	101, 881	3, 457, 110

Philippine Islands and Puerto Rico excluded.
 Includes zinc-copper ore from Arizona and zinc-lead-copper ore from Utah.
 From magnetite-pyrite-chalcopyrite ore.

Mine production of silver in the United States in 1942, by States and sources, in fine ounces, in terms of recovered metals 1

State	Placers	Dry and siliceous ore	Copper ore	Lead ore	Lead- copper ore	Zine ore	Zinc-lead zinc-cop- per, and zinc-lead- copper ores <sup>2</sup>	m-4-1
Alaska Arizona California Colorado Georgia	50, 906 398 40, 635 4, 202	925, 306 1, 086, 247	4, 993, 551 71, 175 3, 189	101, 469 248, 240 61, 717	2,397 301 493	198, 954 2, 304 2, 514	842, 392 1, 538 902, 946	1, 450, 440
Idaho Illinois Michigan Missouri Montana Nevada New Mexico	10, 471 6, 937 19, 980	2, 227, 610 2, 418, 913	27, 390 61, 674 6, 212, 356 558, 330	69, 106 181, 267 434, 355	12,354	127, 670 64, 830 87, 425	5, 345, 830 104 	104 61, 674 69, 106
New York North Carolina Oregon Pennsylvania South Carolina	7,141	315, 135 2, 505 80, 218 5, 064	5, 754 17 3 15, 501	3, 653	3, 565	144, 792	52, 277 40, 012	676, 170 40, 012 8, 259 87, 376 8 15, 501 5, 064
South Dakota	1 59	179, 389 667, 454 1, 875, 712 31 165, 960	34, 671 2, 089 2, 698, 515 176, 348	3, 238 786, 550 712	421 553	2, 278	5, 211, 479 1, 761 25, 406	186, 937 34, 671 672, 781 10, 574, 955 1, 793 369, 038
w young	140, 869	20, 156, 991	15, 017, 173	2, 994, 041	20, 128	630, 767	15, 130, 796	52 54, 090, 765

Philippine Islands and Puerto Rico excluded.
 Includes zinc-copper in Arizona and zinc-lead-copper in Utah.
 From magnetite-pyrite-chalcopyrite ore.

Gold and silver produced in the United States from ore and old tailings in 1942, by States and by methods of recovery, in terms of recovered metals 1

いっぱ まころ 大のでの はたい

lters	Silver (fine ounces)	4, 291, 807 10, 808, 638, 639 616, 797 10, 786, 121 11, 238, 749 107, 654 47, 505 2, 722, 886 27, 772 11, 732 11, 732 11, 733 11, 733	5, 961	11, 487, 913
Orude ore to smelters	Gold (fine ounces)	99,697 13,877 13,877 13,877 28,280 28,281 21,212 11,697 1,69	541	238, 862
Orud	Short tons	27.00 4.24 4.00 6.00 6.00 6.00 6.00 6.00 6.00 6.0	3, 400, 041	3, 565, 937
(from amaldation and combined)	Silver (fine ounces).	668,6 668,6 319,6 32,7 32,3 32,3 32,3 32,4 32,4 32,4 32,4 32,4	39, 090, 472 91, 945	39, 182, 417
Concentrates smelted (from amalgamation and cyanidation and concentrating mills combined)	Gold (fine ounces)	22, 192 16, 673 19, 219 19, 219 19, 219 11, 22, 23 11, 24, 23 11, 346 11, 346 11, 346 11, 346 11, 346 12, 23 13, 442 14, 442	879, 682 2, 668	882, 350
Concentrat gamation concentr	Short tons	3, 004 1, 323, 817 21, 603 140, 500 481, 716 832, 060 337, 736 1, 424 1, 187, 888 71, 482	4, 504, 254 703, 771	5, 208, 025
Ore and old tail-	centrating mills (short tons)	27, 102, 338 455, 338 822, 304 8, 207, 953 8, 107, 858 10, 107, 858 18, 348 19, 907	87, 712, 596 6 3, 960, 833	6 91, 673, 429
o amalgamation and i bullion recovered Silver (fine ounces)		21, 928 103, 946 424, 804 29, 108 11, 835 226, 829 1, 513, 648 226, 829 179, 164 545, 330 18, 178 18, 178	3, 141, 283 7, 399	3, 148, 682
	Gold (fine ounces)	115, 304 46, 040 277, 714 146, 376 142, 886 1, 886	1, 310, 715 11, 421	1, 322, 136
old tailings to ation mills and	Old tail- ings (short tons)	84, 334 625, 564 117, 888 81, 085 2, 675	761, 546 35	761, 581
Ore and old cyanidation	Ore (short tons)	2, 814, 884 509, 347 1, 881, 907 111, 772 234, 051 1, 151, 807 284, 051 1, 44, 887 96, 481 96,	8, 883, 293 106, 062	8, 989, 355
Total ore and old	treated (short tons)	2, 816, 668 2, 5, 7021, 463 1, 707, 386 2, 900, 704 3, 56, 678, 290 9, 383, 379 9, 383, 379 1, 728 1, 484, 384 1, 222, 84 1, 222, 84	5 100, 824, 076 6 4, 166, 226	7 104, 990, 302
	State	Western States and Alaska: Alaska Alaska Arizona California Colorado Idasho Montana Newada Newada New Mexico Oregon Action South Dakota Texas. Utah Washington Wyoming	Eastern States	

1 Illinois, Michigan, Missouri, Philippine Islands, and Puerto Rico excluded.

Excludes 44,190,208 tons of copper ore leached from which no gold or silver was recovered.

Includes 204,378 tons of sing from which silver was recovered.

Includes 87,831 tons of sing from which silver was recovered.

Excludes 87,831 tons of sing from which silver was recovered.

Excludes expper ore leached from Arizons; includes sing from Montana and Utah.

Excludes magnetite-pyrite-chalcopyrite ore from Pennsylvanis, which Bureau of Mines is not at liberty to publish.

Excludes copper ore leached from Arizons; includes slag from Montana and Utah; excludes magnetite ore from Pennsylvania.

THE PROPERTY OF THE PARTY OF TH

Gold and silver produced at amalgamation and cyanidation mills in the United States and percentage of gold and silver recovered from all sources, 1938-421

	Bulli	on and pr (fin	ecipitates re e ounces)	ecovered	I	ercent	of gold	l and si	lver fr	om all :	source	g 1
Year	Amalg	amation	Cyan	idation		gama- on		nida- on	Sme	lting 2	Placers	
	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver
1938 1939 1940 1941 1942	984, 620 985, 717 959, 452 916, 113 623, 319	223, 058 243, 786 248, 112 214, 665 140, 192	962, 788 1, 043, 675 1, 044, 014 1, 005, 031 698, 817	4, 275, 154 4, 556, 336 5, 251, 162 5, 157, 702 3, 008, 490	23. 1 21. 1 19. 7 19. 3 18. 0	0.4 .4 .3 .3	22. 6 22. 3 21. 4 21. 1 20. 2	7. 0 7. 1 7. 5 7. 7 5. 6	26. 4 28. 0 27. 9 28. 3 32. 5	92. 4 92. 2 91. 9 91. 7 93. 9	27. 9 28. 6 31. 0 31. 3 29. 3	0. 2 . 3 . 3 . 3

<sup>1</sup> Illinois, Michigan, Missouri, Philippine Islands, and Puerto Rico excluded.

2 Both crude ores and concentrates.

Gold and silver produced at amalgamation and cyanidation mills in the United States in 1942, by States 1

	Amalgamation			c	yanidat	tion	Perc fron	cent of gold and silver m all sources in State		
State	Ore, old tailings, concen-	covere	ion re- ed (fine ices)	Ore, old tailings, concen- trates,	prec	lion and cipitates overed		gama- on	Cyani	dation
	trates, etc., treated (short tons)	Gold	Silver	sands, slimes, etc., treated (short tons)	Gold	Silver	Gold	Silver	Gold	Silver
Alaska Arizona California Colorado Idaho Montana Newada New Mexico Oregon South Dakota Texas Utah Washington Wyoming Eastern States	2, 814, 884 785, 945 717, 716 109, 072 12, 773 89, 857 500 1, 275, 138 1, 475 125 59 371	327 144, 004 60, 233 16, 580 956 8, 521 170 437 276, 298 95 264 11	29, 010 15, 906 8, 531 207 7, 239 42 95 56, 852 61 87 1	539, 154 1, 006, 361 272, 889 2, 700 239, 166 1, 167, 244 28, 202 6, 838 1, 433, 306 96, 085 94, 827 247, 732	133, 710 86, 132 391 27, 061 134, 064 3, 195 1, 246 244, 421 213 7, 426 3, 943 11, 302	395, 350 13, 202 3, 304 66, 202 1, 506, 409 226, 787 204 122, 312 545, 360 157 18, 091	16. 98 22. 42 17. 45 .65 2. 89 1. 42 .95 52. 92 .35 47. 83 .81	(2) 2.00 .51 .06 (2) .19 .01 .11 30.41  (2)         	18. 02 15. 77 32. 06 18. 42 45. 43 26. 71 2. 70 46. 82 90. 25 1. 90 5. 23	1. 47 27. 26 43 .02 40. 46 33. 54 23 81. 06 (2) 4. 90 6. 94
	5, 809, 245	623, 319	140, 192	5, 240, 830	698, 817	3, 008, 490	18.03	. 26	20. 21	5. 58

Illinois, Michigan, Missouri, Philippine Islands, and Puerto Rico excluded.

2 Less than 0.005 percent.

#### PLACERS

#### DREDGING

Placer gold is obtained largely from gravels handled by connectedbucket floating dredges, which recovered approximately 68 percent of the total output from placers in the United States (Philippine Islands and Puerto Rico excluded) in 1942 and 58 percent in 1941. tity of gold recovered by dredges from the inception of the industry as a commercial factor in 1896 to the end of 1942 is recorded as 19,074,071 ounces, originating by States as follows: California, 11,566,916 ounces; Alaska, 5,158,064 (including the production from two Becker-Hopkins single-dipper dredges and some gold by hydraulicking); Montana, 691,083; Idaho, 612,291; Colorado, 455,195;

Oregon, 467,046; and other States, 123,476. The output in 1942 was 689,069 ounces from 102 dredges, of which California produced 310,937 ounces from 44 dredges; Alaska, 249,868 ounces from 31 dredges; Idaho, 36,631 ounces from 10 dredges; Montana, 31,283 ounces from 7 dredges; Oregon, 21,641 ounces from 6 dredges; and Colorado, 14,523 ounces from 3 dredges.

Connected-bucket floating gold dredges operated in the United States, 1941-42, by companies and districts

#### ALASKA

			Num	
Company	Address	District		
			1941	1942
			1011	1012
		D		
Standard Mines, Inc.1	Ferry	Bonnifield-Nenana	1	
Alluvial Golds, Inc	Fairbanks	Circledo	1	
C. J. Berry Dredging Co	Miller House	ao	1	
		ao	1	
				1.4
Camp Creek Dredging Co	do	do	1	
Camp Creek Dredging Co	do	do		
Ophir Gold Dredging Co	do	do	1	
Brinker-Johnson Co	Fairbanks	Fairbanks	1	
mand Dredging Co  Dphir Gold Dredging Co  Brinker-Johnson Co  United States Smelting, Refining & Mining	do	do	. 8	1.0
( o kairbanks Denartment				
Arctic Circle Exploration, Inc.		Fairhaven	2	1.77
Dury Chaole Duadaina Co	I DAATING	do	1	
Townson Deciding Co	do	do	1	
Boundary Dredging Co	Boundary	Fortymile	1	
Wade Creek Dredging Co	Fairbanks	do	1	
Bristol Bay Mining Co	Goodnews Bay	Goodnews Bay	1	
North American Dredging Co	Flat	Iditarod	Î	ł
Bristol Bay Mining Co. North American Dredging Co. F. E. Riley Investment Co. Sanes Mining Co. Moss & Larson Mining Co.	do	do	1	1.
Janes Mining Co	Ophir	Innoko	1	1
Moss & Larson Mining Co	do	do	1	1
Castleton & Keenan (Kougarok Consolidated	Nome	Kongarok	1	
Com Don Dundging Co	do	do	1	
Throlib Cyndicate	do	Kevnk	1	l
Jngalik Syndicate American Creek Dredging Co	do	Nome	i i	1
Care de Dogo Cold Co	do	do	l î	
asa de Paga Gold Co	Solomon	do	2	١.
Lee Brothers Dreuging Co	Nome	do	1 1	l
American Creek Dredging Co. Lee Brothers Dredging Co. Lee Brothers Dredging Co. Sborn Creek Dredging Co. Tolbert Scott.	do	do	1 1	1
United States Smelting, Refining & Mining				
				1.
Co., Nome Department.	Livengood	Tolovene	1	l
Co., Nome Department. Livengood Placers, Inc Nome Creek Mining Co	Foirbonka	do do	1 1	
Nome Ureek Mining Uo	Nyoa	Tuluksak-Aniak	2	
New York Alaska Gold Dredging Co	Nyac	I uluasan-Alliak		.
		1	47	1

<sup>&</sup>lt;sup>1</sup> Single-dipper dredge.

# Connected-bucket floating gold dredges operated in the United States, 1941-42, by companies and districts—Continued

#### CALIFORNIA

Company	Address	District	Num dree	
Company	Audross	District	1941	1942
			1941	1942
erty Hill Partnership. cha Plana Gold Dredging Co. a Gold Dredging Co. a Consolidated Gold Fields. i Hill Dredging Co. mines Gold Dredging Co. cha Plana Gold Dredging Co. cha Plana Gold Dredging Co. cha Plana Gold Dredging Co. cha Gulch Dredging Co. cha Gulch Dredging Co. cha Gold Dredging Co. cha Plana Gold Dredging Co. cha Consolidate Gold Dredging Co. ction City Mining Co. sta Gold Dredging Co. ction City Mining Co. sta Gold Dredging Co. c	San Francisco	Brandy City 2	1	
che Plene Gold Dredging Co	Lockoford	Diality Clay	-	1.14
a Gold Dradging Co	Collebon	Callahan	1	100
o Consolidated Gold Fields	Can Thomaign	Cananan	- 1	
Hill Drodeing Co.	San Francisco		1	
1 Hill Dredging Co	ao	Camanche	2	
imnes Gold Dreaging Co	do	Cosumnes River	1	4
ital Dredging Co.	do	Folsom	2	
cna Piana Gold Dredging Co	do	:do	1	111
omas Co	do	do	7	
ach Gulch Dredging Co	do	French Gulch	1	
Oro Gold Dredging Co	do	Greenhorn	ĩ	
rman Gold Dredging Co	do	Teo	î	
vo Seco Gold Dredging Co	do	Tone	î	2
cha Plana Gold Dredging Co	Tone	do 3	i	
fornia Gold Dredging Co	Con Francisco	Towner T ind	1	
ation City Mining Co	San Flancisco	Jenny Lind	1	
be Cold Decision Co	Junction City	Junction City	1	
Ra Gold Dredging Co	San Francisco	Kiamath Rico	1	
Frange Gold Dredging Co	ao	La Grange	_ 1	, i i i i i i i i i i i i i i i i i i i
iumne Gold Dreaging Co	do	do	1	
oa Consolidated Gold Fields	do	do	1	
eville Gold Dredging Co	do	Ophir	. 1	1 .
d Hill Dredging Co	do	Oroville	î	
ville Gold Dredging Co	Oroville	do	ī	
oa Consolidated Gold Fields	San Francisco	do	4	
math Dredging Co	Orleans	Orleans		× .
d Gold Dredging Associates	San Francisco	Randsburg	1	
liams Bar Dredging Co	Marysville	Smartville	1	1.75
ced Dredging Co	San Francisco	Snelling	ī	
Joaquin Mining Co	do	do	1 1	0.00
ling Gold Dredging Co	do	do	5	
og Consolidated Gold Fields	do	do	1	10.50
eville Gold Co		Mainite Conton	1	7777
o Concelidated Cold Fields	u0	Verba Dimer	1	7
pa Consolidated Gold Fields evrille Gold Dredging Co  1 Hill Dredging Co  2 Wille Gold Dredging Co  2 Consolidated Gold Fields math Dredging Co  3 Gold Dredging Associates  3 Gold Dredging Associates  3 Gold Dredging Co  3 Gold Dredging Co  3 Gold Dredging Co  4 Gold Dredging Co  5 Gold Fields  6 Gold Fields	ao	ruba Kiver	0	
			47	100
			1	١

Timberline Dredging Co	Fairplay Breckenridge	Beaver Creek Breckenridge	1	1
South Platte Dredging Co	Fairplay	Fairplay	i	i
			2	8

#### IDAHO

			1	
Fisher-Baumhoff Co. (2 Dredges)	Centerville	Boise Basin	2	2
Boise King Placers	Twin Springs	Middle Boise	1	1
Northwest Goldfields	Harvard	Hoodoo	1	1
Idaho-Canadian Dredging Co	Idaho City	Boise Basin	1	1
Snake River Mng. Co	Sunbeam	Yankee Fork	1	1
H. & H. Mines	Elk City	Elk City	1	1
Idaho Warren Dredging Co	North Fork	Gibbonsville	1	1
W. W. Prather	Warren	Warren		1
Mt. Vernon Gold Mng. Co	Elk City	Elk City	1	. 1
Warren Dredging Co	Warren	Pierce	2	
Quartz Creek Dredging Co	Pierce	do	1	
ф-ти				
			12	10
-		'	1	

<sup>&</sup>lt;sup>2</sup> Port Wine district in 1941. <sup>3</sup> Dredge No. 3 was reconstructed and called Dredge No. 5 and moved from Ione district, Amador County, to Butte Creek district, Butte County.

Connected-bucket floating gold dredges operated in the United States, 1941-42, by companies and districts—Continued

#### MONTANA

Company	Address	District	Number of dredges	
			1941	1942
Winston Bros. Co Porter Bros. Corporation Perry-Schroeder Mining Co Emigrant Dredging Co Star Pointer Exploration Co Gold Creek Ming. Co Homer Wilson (Norwegian Dredge)	Helenadodo	Clancey First Chance Missouri River Emigrant First Chance Washington Norris & Norwegian	1 1 1 1 1	1
			7	7

#### NEVADA

and the contract of the contra			
Manhattan Gold Dredging Co	San Francisco	Manhattan	1 1

#### OREGON

The second secon

Western Gold Dredging Co. Pleasant Creek Mining Corporation. Porter and Co. Sunshine Mining Co. (Burnt River Division). Timms Gold Dredging Co. Sumpter Valley Dredging Co. Murphy-Murray Dredging Co.	San Francisco	Canyon Gold Hill Granite Greenhorn do Sumpter Gold Hill	1 1 1 1 1 1	1 1 1 1 1
			7	6

# Gold produced in the United States by connected-bucket floating dredges, 1938-42, in fine ounces

Year	Dredges	California	Alaska	Other States 1	Total
1938	115	375, 296	278, 442	82, 686	736, 424
1939	114	370, 264	304, 995	112, 472	787, 731
1940	122	414, 966	354, 806	134, 377	904, 149
1941	123	418, 282	307, 087	141, 636	867, 005
1942	102	310, 937	249, 868	128, 264	689, 069

<sup>&</sup>lt;sup>1</sup> Colorado, Idaho, Montana, Nevada, and Oregon.

#### OTHER PLACER-MINING METHODS

From 1932 through 1942 dragline and power-shovel excavators operated in connection with dry-land floating amalgamating and sluicing plants have been widely used in placer mining. In 1942 approximately 28 percent of the total output of placer gold, excluding that of Alaska and the Philippine Islands, was recovered at such plants, and 5 percent was produced by old-established mining methods, such as hydraulicking, drift mining, sluicing, and rocking.

Additional information on placer-mining methods may be found in the State reviews in the Minerals Yearbook and Mineral Resources series.

## EMPLOYMENT AND PRODUCTION

Statistics on employment and production in the gold and silver industry are presented for the first time in Minerals Yearbook. Data are given for 1941 only; figures for 1942 are incomplete. Mine and mill employees are classified according to the methods described in this volume in the chapter on Employment and Accidents in the Mineral Industries. Gold, gold-silver, and silver ores are classified on the basis of the methods described in the earlier pages of the chapter on Gold and Silver.

# Employment and production in gold and silver lode mines in the United States in 1941 GOLD ORE

							Employme	nt			
			A verage r	number o	f men				Man-hours		
State or region	Number of mines	1,3%	Mine					Mine			
		Under- ground	Surface 1	Total	Mill	Total	Under- ground	Surface 1	Total	Mill	Total
Western States: Arizona. California. Colorado. Idaho. Montana (incl. Wyoming). Nevada New Mexico. Oregon. South Dakota. Utah. Washington.	- 381 - 172 - 349 - 442 - 43 - 82 - 10 - 24	1, 004 4, 558 1, 658 821 1, 009 1, 176 72 393 1, 369 411 143	265 1, 389 568 232 230 693 13 58 984 65 52	1, 269 5, 947 2, 226 1, 053 1, 239 1, 869 85 451 2, 353 476 195	174 929 535 207 206 330 5 42 270 35 40	1, 443 6, 876 2, 761 1, 260 1, 445 2, 199 90 493 2, 623 511 235	1, 563, 070 9, 071, 197 3, 470, 782 1, 544, 103 1, 797, 535 1, 835, 593 65, 541 669, 668 3, 001, 984 780, 472 245, 597	443, 594 2, 690, 599 1, 287, 834 450, 320 490, 681 1965, 266 17, 280 108, 993 2, 125, 996 166, 339 74, 544	2,006,664 11,761,796 4,738,616 1,994,423 2,288,216 2,800,859 82,821 778,661 5,127,980 946,811 320,141	481, 173 2, 140, 381 1, 191, 904 334, 464 479, 456 828, 307 12, 500 68, 340 601, 443 81, 216 99, 108	2, 487, 837 13, 902, 177 5, 930, 520 2, 328, 887 2, 767, 673 3, 629, 166 95, 321 847, 001 5, 729, 422 1, 028, 027 419, 246
Total Alaska. Eastern States	2,770 54 21	12, 614 832 52	4, 549 360 115	17, 163 1, 192 167	2, 773 336 37	19, 936 1, 528 204	24, 045, 542 2, 083, 040 54, 380	8, 801, 446 975, 840 366, 838	32, 846, 988 3, 058, 880 421, 218	6, 318, 292 754, 768 105, 434	39, 165, 28 3, 813, 64 526, 65
	2, 845	13, 498	5, 024	18, 522	3, 146	21,668	26, 182, 962	10, 144, 124	36, 327, 086	7, 178, 494	43, 505, 58

					Produc	etion						
	Ore (sho	rt tons)				Percer	t of tota from—	l value		Man	-hours	
State or region	Produced	Milled	Gold (fine ounces)	Silver (fine ounces)	Total value <sup>2</sup>	Gold	Silver	Base metals	Per to	n of ore	Per ound	ce of gold silver
								11100015	Mined	Milled	Mined	Milled
Western States: Arizona. California. Colorado. Idaho. Montana (incl. Wyoming). Nevada. New Mexico. Oregon. South Dakota. Utah. Washington.	330, 354 695, 598 1, 250, 607 18, 305 87, 748 1, 711, 744	774, 538 3, 828, 911 1, 225, 243 325, 343 642, 238 1, 215, 961 13, 923 80, 216 1, 711, 739 252, 595 139, 731	130, 298 646, 386 277, 160 62, 657 140, 167 205, 453 4, 360 33, 542 600, 544 42, 171 37, 508	213, 360 985, 692 401, 609 245, 418 390, 653 518, 177 18, 036 96, 607 170, 764 130, 260 175, 011	\$5, 005, 719 23, 376, 410 10, 218, 342 2, 385, 221 5, 225, 582 7, 575, 143 186, 119 1, 259, 716 21, 140, 776 1, 635, 388 1, 444, 066	91. 1 96. 8 94. 9 91. 9 93. 9 94. 9 93. 2 99. 4 90. 3 90. 9	3.0 3.0 2.8 7.3 5.3 4.9 6.9 5.5 5.7 8.6	5.9 .2 2.3 .8 .8 .2 11.1 1.3	2. 51 3. 06 3. 84 6. 04 3. 29 2. 24 4. 52 8. 87 3. 00 2. 88 1. 80	0. 62 . 56 . 97 1. 03 . 75 . 68 . 90 . 85 . 35 . 32 . 71	5. 84 7. 21 6. 98 6. 47 4. 31 3. 87 3. 70 5. 98 6. 65 5. 49 1. 51	1. 88 1. 34 1. 13 1. 68 1. 33 1. 06 . 78 4. 51 . 64
TotalAlaska	10, 483, 920 4, 480, 364 152, 833	10, 210, 438 4, 480, 332 152, 833	2, 180, 246 203, 855 19, 033	3, 345, 587 123, 850 9, 081	79, 452, 178 7, 312, 993 672, 762	96. 0 97. 6 99. 0	3.0 1.2 1.0	1.0 1.2	3. 13 . 68 2. 76	.62 .17 .69	5. 94 9. 33 14. 98	1. 34 2. 31 3. 75
	15, 117, 117	14, 843, 603	2, 403, 134	3, 478, 518	87, 437, 933	96. 2	2.8	1.0	2. 40	. 48	6. 18	1.41

See footnotes at end of table.

# Employment and production in gold and silver lode mines in the United States in 1941—Continued GOLD-SILVER ORE

							Employme	nt			
	Number		Average r	umber o	of men				Man-hours		
State or region	of mines		Mine					Mine	<del></del>		
		Under- ground	Surface 4	Total	Mill	Total	Under- ground	Surface 1	Total	Mill	Total
Western States: Arizona. California. Colorado Idaho. Montana Nevada. New Mexico. Oregon Utah. Washington	68 21 48 16 76 141 22 5 33 5	259 205 282 23 208 778 180 23 262	70 58 91 44 48 169 32 9	329 263 373 67 256 947 212 32 331 5	21 50 123 27 4 128 28 7	350 313 496 94 260 1,075 240 39 331	320, 806 339, 322 569, 537 28, 222 317, 082 1, 369, 123 417, 056 51, 535 421, 084 470	59, 060 78, 952 230, 646 86, 116 91, 832 295, 479 74, 384 18, 625 115, 816	379, 866 418, 274 800, 183 114, 338 408, 914 1, 664, 602 491, 440 70, 160 536, 900 470	55, 166 100, 000 272, 440 69, 708 8, 000 355, 846 78, 070 13, 000	435, 032 518, 274 1, 072, 623 184, 046 416, 914 2, 020, 448 569, 510 83, 160 536, 900 470
Total	435	2, 225	590	2, 815	388	3, 203	3, 834, 237	1, 050, 910	4, 885, 147	952, 230	5, 837, 377
	435	2, 225	590	2, 815	388	3, 203	3, 834, 237	1, 050, 910	4, 885, 147	952, 230	5, 837, 377

					Produc	tion						
<b>9</b> 4.4	Ore (sho	ort tons)				Percer	nt of tota from—			Man	-hours	
State or region	Produced	Milled	Gold (fine ounces)	Silver (fine ounces)	Total value 3	Gold	Silver	Base metals	Per to	n of ore		ce of gold silver
								Inclass	Mined	Milled	Mined	Milled
Western States: Arizona California Colorado Idaho Montana Nevada New Mexico Oregon Utah Washington	138, 611 117, 983 270, 267 82, 465 121, 902 416, 981 89, 430 9, 753 199, 866 87	100, 860 112, 107 264, 943 81, 202 7, 859 332, 993 84, 711 7, 363	13, 187 28, 716 27, 067 5, 566 11, 277 50, 693 11, 598 2, 583 12, 091 32	526, 518 736, 469 622, 763 296, 475 700, 663 2, 424, 067 728, 462 166, 126 946, 277 1, 216	\$926, 065 1, 530, 966 1, 611, 065 409, 383 1, 113, 635 3, 576, 384 924, 930 212, 141 1, 543, 265 2, 139	49. 8 65. 6 58. 8 47. 6 35. 4 49. 6 43. 9 42. 6 27. 4 52. 4	40. 4 34. 2 27. 5 51. 5 44. 7 48. 2 56. 0 55. 7 43. 6 40. 4	9. 8 .2 13. 7 .9 19. 9 2. 2 .1 1. 7 29. 0 7. 2	2. 74 3. 55 2. 96 1. 39 3. 35 3. 99 5. 50 7. 17 2. 69 5. 40	0. 55 . 89 1. 03 . 86 1. 02 1. 07 . 92 1. 77	0.70 .55 1.23 .38 .57 .67 .66 .42 .56	0. 30 . 15 . 43 . 27 . 46 . 22 . 11 . 17
Total	1, 447, 375	992, 038	162, 810	7, 149, 036	11, 849, 973	48. 1	42. 9	9.0	3. 38	. 96	. 67	. 2
	1, 447, 375	992, 038	162, 810	7, 149, 036	11, 849, 973	48. 1	42, 9	9.0	3.38	. 96	. 67	. 23

See footnotes at end of table.

# Employment and production in gold and silver lode mines in the United States in 1941—Continued SILVER ORE

		No.						Employme	nt			
		N		Average r	umber o	of men				Man-hours		
	State or region	Number of mines		Mine					Mine			
			Under- ground	Surface 1	Total	Mill	Total	Under- ground	Surface 1	Total	Mill	Total
California		72 19 46 31 69 129	147 9 95 853 218 355 13	39 25 22 125 51 76	186 34 117 978 269 431	1 2 27 75 31 21 1	187 36 144 1,053 300 452 14	112, 596 10, 206 163, 702 1, 811, 858 391, 899 463, 864 2, 350	32, 688 14, 679 37, 030 257, 506 116, 260 67, 560	145, 284 24, 885 200, 732 2, 069, 364 508, 159 531, 424 2, 350	2,000 2,000 62,800 157,043 72,712 40,656 55	. 147, 284 - 26, 884 - 263, 532 2, 226, 407 580, 87 572, 080 2, 400
Texas Utah		 34 8	242 277 9	20 37 2	262 314 11	55 1	317 314 12	591, 440 436, 492 5, 565	50, 664 133, 309 1, 920	642, 104 569, 801 7, 485	156, 000 2, 000	798, 10 569, 80 9, 48
Total		 425	2, 218	397	2, 615	214	2, 829	3, 989, 972	711, 616	4, 701, 588	495, 266	5, 196, 85
		425	2, 218	397	2, 615	214	2, 829	3, 989, 972	711, 616	4, 701, 588	495, 266	5, 196, 85

					Produc	tion						
Ober annual and	Ore (sho	ort tons)				Percen	t of total			Man	-hours	
State or region	Produced	Milled	Gold (fine ounces)	Silver (fine ounces)	Total value 2	Gold	Silver	Base metals	Per to	n of ore		ce of gold silver
								metais	Mined	Milled	Mined	Milled
Western States: Arizona	36, 375 2, 262 68, 471 490, 691 122, 684 116, 335 282	3, 992 2, 152 45, 729 480, 902 47, 882 86, 326 50	713 27 967 433 5, 170 5, 002 8	455, 936 19, 225 1, 200, 260 9, 869, 309 1, 823, 971 1, 242, 526 7, 732	\$374, 732 17, 814 1, 025, 659 7, 672, 103 1, 644, 374 1, 074, 020 6, 255	6.7 5.3 3.3 .2 11.0 16.3 4.5	86. 5 76. 7 83. 2 91. 5 78. 9 82. 3 87. 9	6.8 18.0 13.5 8.3 10.1 1.4 7.6	3. 99 11. 00 2. 93 4. 22 4. 14 4. 57 8. 33	0.50 .93 1.37 .33 1.52 .47 1.10	0. 32 1. 29 . 17 . 21 . 28 . 43 . 30	0.06 .11 .08 .02 .08 .05
Texas 3 Utah Washington	140, 739 94, 208 2, 492	140, 503 2, 300	304 3, 895 53	1, 095, 750 1, 256, 541 10, 723	811, 917 1, 327, 120 9, 701	1. 3 10. 8 19. 1	96. 0 67. 3 78. 6	2. 7 21. 9 2. 3	4. 56 6. 05 3. 00	1.11	. 59 . 45 . 69	.14
Total	1, 074, 539	809, 836	16, 572	16, 981, 973	13, 963, 695	4.2	86. 5	9. 3	4. 38	. 61	. 28	.04
	1, 074, 539	809, 836	16, 572	16, 981, 973	13, 963, 695	4. 2	86. 5	9. 3	4.38	. 61	. 28	.04

See footnotes at end of table.

# Employment and production in gold and silver lode mines in the United States in 1941—Continued SUMMARY

•							Employme	nt	- San		
	Manahan		Average 1	number o	f men				Man-hours		
State or region	Number of mines		Mine					Mine			
		Under- ground	Surface 1	Total	Mill	Total	Under- ground	Surface i	Total	Mill	Total
Western States: Arizona. California. Colorado. Idaho. Montana (incl. Wyo.) Nevada. New Mexico. Oregon. South Dakota Texas. Utah Washington Total.	4 803 4 465 4 217 4 490 4 698 4 73 87 10 4 91 45	1, 410 4, 772 2, 035 1, 697 1, 435 2, 309 265 416 1, 369 242 950 157	374 1, 472 681 401 329 938 45 67 984 20 171 54	1, 784 6, 244 2, 716 2, 098 1, 764 3, 247 310 483 2, 353 262 1, 121 211	196 981 685 309 241 479 34 49 270 55 35 41	1, 980 7, 225 3, 401 2, 407 2, 005 3, 726 344 532 2, 623 317 1, 156 252	1, 996, 472 9, 420, 725 4, 204, 021 3, 884, 183 2, 506, 516 3, 668, 580 484, 947 721, 203 3, 001, 984 591, 440 1, 638, 048 251, 632	535, 342 2, 784, 530 1, 535, 510 793, 942 698, 773 1, 328, 305 91, 664 127, 618 2, 125, 996 50, 664 415, 464	2, 531, 814 12, 204, 955 5, 739, 531 4, 178, 125 3, 205, 289 4, 996, 885 576, 611 848, 821 5, 127, 980 642, 104 2, 053, 512 328, 096	538, 339 2, 242, 381 1, 527, 144 561, 215 560, 168 1, 224, 809 90, 625 81, 340 601, 443 156, 000 81, 216	3, 070, 153 14, 447, 336 7, 266, 675 4, 739, 340 3, 765, 457 6, 221, 604 667, 236 930, 161 5, 729, 423 798, 104 2, 134, 728 429, 204
Total Alaska Eastern States	4 3, 577 54 21	17, 057 832 52	5, 536 360 115	22, 593 1, 192 167	3, 375 336 37	25, 968 1, 528 204	31, 869, 751 2, 083, 040 54, 380	10, 563, 972 975, 840 366, 838	42, 433, 723 3, 058, 880 421, 218	7, 765, 788 754, 768 105, 434	50, 199, 51 3, 813, 64 526, 65
	4 3, 652	17, 941	6, 011	23, 952	3,748	27, 700	34, 007, 171	11, 906, 650	45, 913, 821	8, 625, 990	54, 139, 81

					Produc	tion						
Chada an analan	Ore (short tons)  Percent of total value from—  M							Man	Ian-hours			
State or region	Produced	Milled	Gold (fine ounces)	Silver (fine ounces)	Total value 2	Gold	Silver	Base metals	Per to	n of ore	Per oun and	ce of gold silver
									Mined	Milled	Mined	Milled
Western States: Arizona. California. Colorado. Idaho. Montana (incl. Wyo.). Nevada. New Mexico. Oregon. South Dakota. Texas. Utah. Washington.	I 040 184	879, 390 3, 943, 170 1, 535, 915 887, 447 697, 979 1, 635, 684 87, 579 1, 711, 739 140, 503 252, 595 142, 031	144, 198 675, 129 305, 194 68, 656 156, 614 261, 148 15, 966 36, 125 600, 544 58, 157 37, 593	1, 195, 814 1, 741, 386 2, 224, 632 10, 411, 202 2, 915, 287 4, 184, 770 754, 230 262, 733 170, 764 1, 095, 750 2, 333, 078 186, 950	\$6, 306, 516 24, 925, 190 12, 855, 066 10, 466, 707 7, 983, 591 12, 225, 547 1, 117, 304 1, 471, 857 21, 140, 472 811, 917 4, 505, 773 1, 455, 906	80. 0 94. 8 83. 1 23. 0 68. 7 74. 8 50. 0 85. 9 99. 4 1. 3 45. 2 90. 4	13. 5 5. 0 12. 3 70. 7 26. 0 24. 3 48. 0 12. 7 96. 0 36. 8 9. 1	6.5 .2 4.6 6.3 5.3 2.0 1.4 2.7 18.0	2. 59 3. 08 3. 65 4. 62 3. 41 2. 80 5. 34 8. 70 3. 00 4. 56 3. 30 1. 82	0. 61 . 57 . 99 . 63 . 80 . 75 . 92 . 93 . 35 1. 11 . 32 . 71	1.89 5.05 2.27 .40 1.04 1.12 .75 2.84 6.65 1.83 .86	1. 14 . 98 . 74 . 05 . 47 . 40 . 13 . 42 . 78 . 14 4. 51
Total	13, 005, 834 4, 480, 364 152, 833	12, 012, 312 4, 480, 332 152, 833	2, 359, 628 203, 855 19, 033	27, 476, 596 123, 850 9, 081	105, 265, 846 7, 312, 993 672, 762	78. 5 97. 6 99. 0	18. 6 1. 2 1. 0	2.9 1.2	3. 26 . 68 2. 76	.65 .17 .69	1. 42 9. 33 14. 98	. 35 2. 31 3. 75
	17, 639, 031	16, 645, 477	2, 582, 516	27, 609, 527	113, 251, 601	79.8	17.3	2.9	2.60	. 52	1. 52	.38

Includes open-cut workers.
 Includes value of base metals recovered.
 Included with gold-silver ore from Oregon.
 A mine producing more than 1 class of ore is counted but once in arriving at total for all classes.

					E	mployment					Pro	duction	
State of region	Number of mines	Av	erage num	ber of me	n		Man	-hours		G-14	Q21	Matal.	Man-hours
		Dredg- ing	Hydrau- licking	Other 1	Total	Dredging	Hydrau- licking	Other	Total	Gold (ounces)	Silver (ounces)	Total value	per ounce gold and silver
Western States: Arizona California Colorado Idaho Montana Nevada New Mexico Oregon South Dakota Utah Washington Wyoming	103 153 41 12	70 3, 817 276 437 435 110 33 541	1 453 131 245 36 3 3 179 179	194 852 254 438 257 196 96 115 48 17 62	265 5, 122 661 1, 120 728 309 129 835 49 32 88 35	142, 240 7, 137, 253 444, 804 740, 496 709, 993 250, 483 45, 740 1, 029, 120 11, 280 11, 280 19, 200	360 576, 694 142, 632 193, 663 31, 684 552 146, 034 160 128	116, 880 981, 123 204, 784 270, 554 239, 093 169, 852 115, 908 89, 888 21, 560 14, 928 22, 392 3, 208	259, 480 8, 695, 070 792, 220 1, 204, 713 980, 770 420, 887 161, 648 1, 265, 042 21, 720 28, 336 33, 672 22, 408	11, 931 718, 013 30, 377 72, 395 61, 611 36, 897 2, 488 60, 430 93 629 629 540 447	2, 205 65, 475 5, 687 17, 408 10, 035 14, 033 284 11, 205 7 90 90 50	\$419, 153 25, 177, 015 1, 067, 239 2, 546, 204 2, 163, 521 1, 301, 374 87, 282 2, 123, 018 3, 260 22, 079 18, 964 15, 681	18. 35 11. 10 21. 96 13. 41 1 13. 69 8. 26 58. 31 17. 66 217. 20 39. 41 53. 45
TotalAlaskaEastern States	2, 536 799 14	5, 779 2, 424 13	1,050 971	2, 544 570 17	9, 373 3, 965 30	10, 543, 889 3, 796, 336 25, 878	1, 091, 907 776, 800	2, 250, 170 684, 000 6, 960	13, 885, 966 5, 257, 136 32, 838	995, 851 491, 581 203	126, 569 67, 544 15	34, 944, 790 17, 253, 366 7, 116	12, 37 9, 40 150, 63
	3, 349	8, 216	2, 021	3, 131	13, 368	14, 366, 103	1, 868, 707	2, 941, 130	19, 175, 940	1, 487, 635	194, 128	52, 205, 272	11. 40

# Summary—Employment and production in all gold and silver mines in the United States in 1941

		Emp	oloyment			Produ	iction			
State or region	Number of mines						Percent o	f total val	1e from—	Man-hours per ounce
	or mines	Men	Man-hours	Gold (ounces)	Silver (ounces)	Total value 2	Gold	Silver	Base metals	gold and silver mined
Western States:     Arizona     California     Colorado     Idaho     Montana     Nevada     New Mexico     Oregon     South Dakota     Texas     Utah     Washington     Wyoming 4	\$ 789 \$ 741 \$ 815 \$ 776 \$ 176 240 51 4 103	2, 049 11, 366 3, 377 3, 218 2, 492 3, 556 439 1, 318 2, 402 262 1, 153 299 35	2, 791, 294 20, 900, 025 6, 531, 751 5, 382, 838 4, 186, 059 5, 417, 772 738, 259 2, 113, 863 5, 149, 700 642, 100 2, 081, 848 361, 768 22, 408	156, 129 1, 393, 142 335, 571 141, 051 218, 225 298, 045 18, 454 96, 555 600, 637 304 55, 786 38, 133	1, 198, 019 1, 806, 861 2, 230, 319 10, 428, 610 2, 925, 322 4, 198, 803 754, 514 273, 938 170, 771 1, 095, 750 2, 333, 168 187, 040	\$6, 725, 669 50, 102, 205 13, 922, 305 13, 012, 911 10, 147, 112 13, 526, 921 1, 204, 586 3, 594, 875 21, 143, 732 4, 527, 852 1, 474, 870 15, 681	81, 2 97, 3 84, 4 37, 9 75, 3 77, 1 53, 6 94, 0 99, 4 1, 3 45, 4 90, 5	12. 7 2. 6 11. 4 57. 0 20. 5 22. 1 44. 5 5. 4 98. 0 36. 6 9. 0	6. 1 . 1 4. 2 5. 1 4. 2 . 8 1. 9 . 6	2. 00 6. 55 2. 55 . 50 1. 33 1. 22 . 90 5. 70 6. 65 . 88 1. 60 45. 00
TotalAlaska Eastern States	853	31, 966 5, 157 197	56, 319, 689 8, 316, 016 454, 056	3, 355, 479 695, 436 19, 236	27, 603, 165 191, 394 9, 096	140, 210, 636 24, 566, 359 679, 878	83. 8 99. 1 99. 0	14.0 .6 1.0	2.2	1.8 9.3 16.0
	7,001	37, 320	65, 089, 761	4, 070, 151	27, 803, 655	165, 456, 873	86.1	11.9	2.0	2.0

Includes employees in underground placers, small-scale hand operations, and surface shops and yards.
 Includes value of base metals recovered.
 A mine producing more than 1 class of ore is counted but once in arriving at total for all classes.
 Placer mines only; data on lode mines included with Montana.

# WORLD ASPECTS

# WORLD PRODUCTION

According to the Bureau of the Mint, the world output of gold and silver from 1493 to 1941 is 1,415,496,883 fine ounces of gold valued at \$33,321,716,914 and 17,507,210,287 fine ounces of silver valued at \$15,543,504,556 (see figs. 2 and 3).




FIGURE 2.—World production of gold, 1900-42. (Figures for 1942 are preliminary.)




FIGURE 3.—World production of silver, 1900-42. (Figures for 1942 are preliminary.)

World production of gold, 1938-42, by countries, in fine ounces 1

Country	1938	1939	1940	1941	1942
orth America:					
United States:	4 047 000	4 600 567	4 000 070	4 000 007	9 E09 00
Continental 2 Puerto Rico	4, 245, 368	4, 620, 567 35	4, 862, 979	4, 832, 067	3, 583, 08
Canada	4,725,117	5, 094, 379	5, 311, 145	5, 345, 179	4, 829, 81
Central America and West Indies:	17 004	19 001	19 590		<b>(A</b> )
Costa Rica	17, 994 5 3, 889 5, 275	13, 261 4 3, 851 6, 304	13, 538 4 1, 251 6, 914	<sup>2</sup> 12, 760 <sup>5</sup> 607	(4) # 19
Cuba Dominican Republic (exports) Guatemala Honduras	5, 275	6,304	6, 914	15, 614	(A)
Guatemala	5 466	5,058	4,447	2, 560	(4) 22, 08 (4)
Honduras	21, 879 44, 301	22, 216	23, 173 164, 355	22, 822 209, 430	(4)
Panama	6,879	100, 182 3, 774	2, 634 6 51, 195	2, 115	(4)
Salvador	6,879 12,065	6 16, 424	6 51, 195	2, 115 6 32, 593	6 30, 19
Other countries 3	48,300	(4) 841, 642	883 117	(4) 799, 975	(4) 801 39
Honduras Nicaragua Panama Salvador Other countries 3 Mexico Newfoundland	48,300 923,819 24,246	20, 316	883, 117 21, 786	21, 194	801, 32 15, 75
	10, 085, 000	10, 798, 000	11, 397, 000	11, 347, 000	9, 557, 00
outh America:					
Argentina	8, 423	12, 249 7 7, 884	12,860 5 11,749	17, 136	(4)
Argentina Bolivia	8, 423 7 9, 255	7 7, 884	5 11, 749	1 58 158	(4) 5 5, 90
Brazil	216,600	290, 096 329, 453	318, 935 342, 830	<sup>3</sup> 260, 000 268, 838	(4) 187, 33
Chile	294, 033 520, 717 74, 042	329, 453 570, 017 85, 352	342, 830 631, 927 52, 942	268, 838 656, 019 70, 264	(i) ., u
Ecuador	74,042	85, 352	52, 942	70, 264	(1)
Guiana: British	38, 482	29 472	35, 745	90 132	18, 57
French	40, 638	38, 473 37, 606	32, 561	29, 138 5 34, 281 8 12, 000	s 25, 60
French Netherlands (Surinam)	14, 154 260, 326	14,812	32, 561 5, 921	8 12,000	(4) (4)
Peru	260, 326	269, 355	281, 529	285, 189	· (2)
Uruguay Venezuela	657 114, 985	1, 608 146, 608	1, 762 146, 792	1, 364 130, 382	(4) (4)
	1,592,000	1, 802, 000	1, 886, 000	1, 773, 000	1, 593, 00
rope:	200	6, 690	7, 330	(4)	(9)
Bulgaria Czechoslovakia Finland	10,000	6, 690 10, 000	<sup>3</sup> 10,000	(4)	(4)
Finland	3, 858	4, 822	(4) (4)	(4) (4) (4)	(f) (f) (f)
France. Germany Austria. Hungary	87, 354	8 85, 000			
Austria	8,650	(4)	(4)	(4)	(4)
Hungary	5, 655	5, 079	(4)	999	(1) (1)
		(4) (4)	(i)		82
Portugal	6, 186	5, 948	3 10,000	(4)	
Norway Portugal Rumania	6, 186 157, 924	211.496	\$ 10,000 130,760 \$ 15,000	(4)	
Snain	6.955	<sup>3</sup> 30, 000 216, 149	* 15,000 197,995	(4)	270, 20
Switzerland	1, 125	1, 447	(4)	( <del>)</del>	(1)
U. S. S. R. <sup>3</sup>	5, 236, 000	(4)	5, 787, 000	(4)	8
Sweden Switzerland U. S. S. R. <sup>4</sup> United Kingdom	1, 125 5, 236, 000 2, 428 78, 318	(4) 71, 503	8 75, 000	(4)	(4)
Yugoslavia				8 4. 500, 000	(4)
	5, 844, 000	5, 665, 000	6, 310, 000	4. 500, 000	(4)
a: Burma	1,209	(9)	(9)	(9)	(9)
China Manchuria 7 Chosen Chosen	(9)	(4)	³ 377, 000		(4)
Manchuria 7	(2)	075 000	(4)	8	2
Chosen	948, 447 \$ 29, 245	975, 000 5 16, 393	13, 621		8
Cyprus India, British Indochina Japan	321, 138	9 316, 504	9 289, 357	285, 945	• 257, 00
Indochina	321, 138 8, 745 8 760, 000	8,070 3 836,000	8,038 (	(4) (4)	8
Japan Malay States:	* 760,000	* 836,000	(4)	(9)	(•)
Fodowatad	40, 209	40, 283	35, 689	(4)	(4)
Straits Settlements	5	8	6	(4)	(4)
Unfederated	581	880	479 80 042	(2)	8
	76, 443 903, 265	81, 183	89, 942 1, 140, 126	1, 144, 332	158, 72
Netherlands Indies		1, UZU, 1TU	1, 110, 120	-,, 000	100, 12
Straits Settlements	18, 520	17, 261	12, 280	(*)	(*)
	18, 520 145, 000	1, 040, 146 17, 261 (4)	12, 280	8	-83
Netherlands Indies. Philippine Islands. Sarawak. Taiwan. Thailand (Siam).	18, 520 145, 000 13, 620	17, 261 (4) 12, 711	12, 286 (1) 12, 717 ·		8

See footnotes at end of table.

World production of gold, 1938-42, by countries, in fine ounces 1—Continued

Country	1938	1939	1940	1941	1942
frica:					
Bechuanaland	19, 111	17, 219	18, 015	14, 509	15, 441
Belgian Congo Ruanda and Urundi	455, 264	494, 642	618, 565	10 561, 030	10 499, 944
Ruanda and Urundi	17, 994	29, 386	(4)	(10)	(10)
Camerouns, French	15 542	(4)	(4)	(4)	(4)
Egypt French Equatorial Africa French West Africa (exports)	2, 162	3,877	7, 344	2,868	(4)
French Equatorial Africa	40,028	(4) <sup>'</sup>	(4)	(4)	<u> </u>
French West Africa (exports)	127, 220	(4)	133, 394	1 65	745
Gold Coast	674 927	782, 271	866, 326	886,000	4
Kenya Colony Liberia (exports)	70,500	77,000	77, 243	(4)	(4)
Liberia (exports)	1,902	6, 536	9, 661	20, 370	740
Madagascar Morocco, French	13, 770	3 14, 000	11, 580	10, 995	74
Morocco, French	7,491	(4)	(4)	(4)	24
Nigeria	24.815	25, 794	25, 617	(4)	24
Portuguese East Africa	11,654	13, 386	13, 386	3 13, 500	24
Rhodesia:		10,000	10,000	10,000	(-)
Northern	1,092	4, 645	(4)	(4)	(4)
Southern	21/ 079	795, 613	826, 485	790, 442	(4) 760, 030
Sierra Leone South-West Africa	30, 012	33, 657	32, 676	(4)	700,000
South-West Africa	1,796	1,619	1, 358	304	(4) (4) (4)
Sudan	8,866	7, 510	6,606	(4)	$\Sigma$
Swaziland *	1, 246	983	1,080		<u> </u>
Tongonyiko	01 057	130, 366	143, 693	144, 312	52
Trando	20,507	15, 115	11,060		52
Tanganyika Uganda Union of South Africa	10 161 200	10 010 044		9, 505	14 100 01
Other countries.	(4)	12,819,344	14, 037, 741 (4)	14, 386, 361	14, 120, 617 (4)
한당점점 하나는 사이를 보다면	14, 629, 000	15, 490, 000	16, 933, 000	17, 198, 000	16, 709, 000
ceania:					
Australia:					
New South Wales		87, 189	89, 839	88, 091	77, 248
Northern Territory	12, 378	16,586	22, 423	(4)	(4)
Queensland	151, 432	147, 248	154,011	(4)	(4)
South Australia	5, 292	3,930	3, 270	1.679	( <del>4</del> )
Victoria	144, 243	156, 522	163, 662	149, 768	(4)
Western Australia	1, 167, 791	1, 214, 238	1, 191, 481	1, 109, 318	848, 180
Fiji	92, 362	110,000	111, 338	118, 681	(4)
New Guinea	236, 133	246, 214	294, 794	(4), 001	(4)
New Zealand	152, 050	178, 955	195, 665	190,000	<b>3</b>
Papua	33, 249	28, 164	35,000	(4)	745
Tasmania	22, 200	19, 984	19, 171	19, 908	(4)
	2, 106, 000	2, 209, 000	2, 281, 000	2, 075, 000	1, 724, 000
	37, 922, 000	39, 853, 000	42, 831, 000	40, 836, 000	37, 000, 000

¹ Preliminary world gold production table prepared with revisions and adjustments by B. B. Waldbauer, Foreign Minerals Division, and Frederick Betz, Metal Economics Division, Bureau of Mines, in cooperation with the Office of the Director of the Mint. Figures used were derived in part from the Statistical Yearbook of the League of Nations and from the American Bureau of Metal Statistics. No official statistics are issued by Government of U. S. S. R., consequently figures released by the various authorities vary widely and are irreconcilable. In some countries accurate figures are not possible to obtain owing to clandestine trade in gold.

² Refinery production.
³ Approximate production.
³ Approximate production.
³ Data not available. Estimate included in total.
⁵ Exports.

<sup>Data not available. Estimate included in total.
Exports.
Imports into United States.
Purchases by the State Central Bank.
Conjectural figure published by the American Bureau of Metal Statistics (New York), Annual Issue.
Beginning with 1939, Burmese production included with British India.
Beginning with 1941, production of Ruanda and Urundi included with Belgian Congo.</sup> 

World production of silver, 1938-42, by countries, in fine ounces 1

Country	1938	1939	1940	1941	1942
North America:					
United States 2	61, 688, 834	63, 871, 972	68, 286, 535	71, 075, 932	55, 859, 658
Canada Central America and West	22, 219, 195	23, 163, 629	23, 833, 752	21, 754, 798	20, 671, 986
Indies:			100		
Honduras	3, 335, 070	4, 118, 864	3, 899, 164	3, 488, 677	3, 478, 831
Other countries	965, 000	681,000	(4)	(4)	(4)
Mexico Newfoundland	81, 018, 809	75, 870, 575	82, 640, 074	78, 363, 961	84, 864, 616
Newloundland	1, 663, 623	1, 421, 060	1, 494, 066	1, 657, 342	1, 106, 121
	170, 891, 000	169, 127, 000	180, 754, 000	176, 941, 000	166, 581, 000
South America:			44		
Argentina	2, 636, 361	3, 125, 756	3, 242, 200	3, 978, 400	(4) 8, 121, 438
Bolivia (exports)	6, 373, 660	7, 241, 312	5, 626, 380	7, 348, 695	8, 121, 438
Brazil Chile	25, 585 1, 375, 530	27, 075 1, 180, 902	24, 694 1, 515, 563	21, 170 1, 242, 240	$\mathbb{R}$
Colombia	192, 880	242, 628	260, 310	271, 115	K
Ecuador.	89, 111	103, 331	105, 000	116, 836	(4)
Ecuador Guiana, British	5, 060	(4)			(4)
Peru	20, 552, 816	18, 802, 075	19, 916, 774	15, 101, 300	(4)
	31, 251, 000	30, 728, 000	30, 691, 000	28, 100, 000	28, 512, 000
Europe:					
Bulgaria (estimated)	13, 000	(4)	(4)	(4) (4)	(4)
Bulgaria (estimated) Czechoslovakia	1, 190, 326	8	(4)	(4)	(4)
Finland	57, 900	61,000	(4)	(4) (4)	(4)
France	³ 565, 000	<sup>3</sup> 565, 000	~ (4)		(4)
Germany	7, 010, 000	(4)	(4)	(4)	(4)
Grana 3	335,000	(4)	(4)	(4)	(4)
Hungary	46, 632	`51, 600	(4)	<u> </u>	(4)
Italy Norway	812, 481	880,000	(4)	(4)	(4)
Norway	250, 776	295, 787	(9)	(4)	(2)
Poland Portugal	62, 244 16, 742		(4)	2	(2)
Rumania	819, 876	712, 731	500, 204	<b>X</b>	(4) 745, 543
Spain	237, 658	(4)	(4)	(4)	(4)
Sweden	1, 123, 861	1, 122, 865	(4) 745, 894	(4)	(4)
Sweden U. S. S. R. <sup>3</sup>	8, 022, 000	(4)	(*)	(4)	(4)
United Kingdom	107, 985	70, 818	(4)	(4) (4) (6)	0000
Yugoslavia	2, 524, 123	2, 293, 634	(4)	(1)	(9)
	23, 196, 000	21, 978, 000	<sup>8</sup> 20, 000, 000	(4)	(4)
Asia:	F 000 000	0 155 000	<b>(</b> ()		<i>(</i> 1)
Burma China	5, 920, 000	6, 175, 000		<b>X</b>	X
Chosen	X	<b>X</b>			N N
Cymrue	6 199, 719	6 103, 953	`58, 341	(4)	(4)
Federated Malay States Hong Kong India, British Indochina	3, 500		(4)	(4)	(1)
Hong Kong	111,070	(4)		92	(2)
India, British	22, 295	22,745	1,736	1 12	
Janan	2, 411 3 10, 100, 000	(4)	(4)	<b>X</b>	
Netherlands Indies. Philippine Islands. Sarawak	579, 297	618,026	1, 506, 166	(4)	(4)
Philippine Islands	1, 167, 612	1, 350, 099	1, 299, 199	1, 260, 097	231, 197
Sarawak Taiwan	1,660	700			(2)
Turkey 7	350,000	575, 000	575,000	(4)	(4)
	21, 623, 000	23, 115, 000	22, 868, 000	(4)	(4)
Africa:					
Algeria	7 90, 000	7 85, 000	(4)	(4)	(4)
Bechuanaland	1, 127	813	1,207	949	1, 267
Belgian Congo Gold Coast	3, 121, 559 23, 000	2,800,000	3, 536, 582 (4)	l . X	X
Kenya Colony	11, 200	* 12,000	13, 626	(f) (f)	99
Morocco, French	11, 200 208, 980	(4)	(4)	///	(4)
Nigeria	(4)	(4)	(4)	(4)	<b>(4)</b>
Portuguese East Africa Rhodesia:	1,808	(4) 2, 319	1,901	(4) 3 2,000	
Northern	88, 237	80, 137	(4) 186, 080	(4) 170, 364	(4)
Southern	166, 417 1, 271	173, 556	186,080	170, 364	163, 776
Sierra Leone South-West Africa	1,271	(4) 587, 000	(4)	(1)	(2)
Concernite	8 673, 500	587,000	7 460,000 25 402	(1)	1 22
Tanganyika Tunisia	16, 473 61, 149	27, 999 (4)	35, 492 (4)	40, 143	X
Uganda	1, 981	1, 376	1.015	1.005	X
Uganda Union of South Africa	1, 981 1, 135, 374	1, 376 1, 182, 516	1, 015 1, 292, 284	1,005 71,461,000	(4) 163, 776 (9) (4) (4) (4) (6) (6) (4)
					(1)
	5, 652, 000	5, 389, 000	6, 130, 000	(4)	()

See footnotes at end of table.

World production of silver, 1938-42, by countries, in fine ounces 1-Continued

Country	1938	1939	1940	1941	1942
Oceania: Australia: New South Wales Queensland South Australia Victoria. Western Australia New Guinea. New Guinea. New Zealand Tasmania	9, 558, 550 3, 533, 490 5, 898 271, 346 12, 380 8 104, 000 357, 709 1, 219, 550	8, 584, 719 3, 885, 963 6, 285 287, 439 (4) 7 175, 015 390, 342 1, 278, 116	7 9, 000, 000 7 3, 450, 000 2, 715 8 6, 500 274, 741 23, 020 199, 084 415, 330 1, 608, 681	(4) 4, 660 (4) 255, 000 7 30, 382 7 125, 000 7 400, 000 1, 326, 738	SSSSSSSSSSSSSSSSSSSSSSSSSSSSSSSSSSSSSS
	15, 063, 000 267, 676, 000	14, 620, 000 264, 957, 000	14, 980, 000 275, 423, 000	(4) 9 262, 854, 000	(4) 3 249, 663, 000

Preliminary world silver production table prepared with revisions and adjustments by B. B. Waldbauer, Foreign Minerals Division, and Frederick Betz, Metal Economics Division, Bureau of Mines, in cooperation with the Office of the Director of the Mint. No official statistics are issued by Government of U. S. S. R., consequently figures released by the various authorities vary widely and are irreconcilable. Philippine Islands excluded.

Approximate production.

Data not available. Estimate included in total.

Conjectural figure published by the American Bureau of Metal Statistics.

Exports.
American Bureau of Metal Statistics (New York), Annual Issue.
Imperial Institute (London), Statistical Summary.
Annual Report of the Director of the Mint (1942).

## REVIEW BY COUNTRIES

Data on gold and silver mining in countries outside the United States were even less complete in 1942 than in 1941. Naturally, the Philippine Islands, with their production of over 1,000,000 ounces of gold in 1941, were removed completely from the picture, and many other countries have such rigid censorship regulations that little or no information has been released since 1939.

#### CANADA

Labor shortage was a primary problem in Canadian gold mines in 1942, but shortage of equipment was severely felt also. Operators were forced to eliminate all but essential development and to hire old men, women, and boys in an effort to keep the Mines open. Thousands left the gold camps to join the armed forces or to work in industrial centers farther south. It is reported that Porcupine lost 10,000 of its 41,000 people and Kirkland Lake 16,000 of its 23,000. By the end of the year half of the gold mines in British Columbia and 16 or 17 in Ontario and Quebec were closed. Output of ore at the great Hollinger mine in Ontario dropped from 5,200 tons daily to 3,500 tons. In the fall, about 600 men from Ontario gold mines were transferred to the Sudbury nickel mines, but the movement appears to have been only partly successful. It is stated that 25 percent of the men quit in a short time because of inadequate housing facilities, lack of qualifications for the Sudbury camp, different mining conditions, and inability to meet physical standards. ever, these difficulties were being overcome, and indications were that the transfer of gold miners to base-metal mines would be more successful in the future.

No order as drastic as L-208 was issued by the Canadian Government. In contrast with the United States, Canada appeared to have adopted the policy of gradual curtailment of gold mining, no doubt in recognition of the great dependence of Canadian economy on the gold industry and the utter ruin that whole communities would face by a sudden shut-down. In July the Government issued an order prohibiting the opening of new gold mines and limiting monthly tonnage in mines then open to the average of the first 4 months of the year. A few months later the Premier stated that action must be taken to curtail gold production further, that plans would be carried out in step with war requirements, and that due regard would be given the industry so that it would function soundly in the postwar period. This policy, together with Allied successes on the war front, created a general feeling of optimism, so that gold stocks on the Toronto exchange remained strong throughout the year.

Gold output in Canada in 1942 declined over 500,000 ounces from 1941, but despite this decrease the value of gold was 47 percent of the value of all metals produced and 33 percent of the value of all minerals produced in the Dominion. Gold lodes supplied 85 percent of the total gold; placers and base-metal deposits, 15 percent. Gold and silver production in 1942 was distributed among the various provinces

as follows:

Pro	/ince:	Gold, fine ounces	Silver, fine ounces
Tiv	Ontario	2, 756, 922	4, 426, 977
	Quebec	1 101 533	1, 649, 292
	British Columbia	470, 254	10, 617, 278
	Saskatchewan	173, 361	2, 603, 748
5-11	Manitoba	138, 666	845, 849
7, 0	Northwest Territories	97, 039	22, 433
	Yukon	79 058	506, 002
	Nova Scotia	12, 950	404
1114	Alberta	32	±0.±

Total 4, 829, 815 20, 671, 986

Ontario produced about 57 percent of Canadian output of gold in 1942. The gold-bearing quartz veins of the Porcupine and Kirkland Lake regions supplied 77 percent of the Province total and about 50 percent of the Dominion lode production. These two camps have increased their reserves in recent years, and the ore bodies show no signs of exhaustion. Gold ore milled in the Province in 1942 totaled 10,548,849 tons compared with 12,129,513 tons in 1941; 14 mills closed during the year.

#### MEXICO

The Republic of Mexico continued to hold first place as the world's leading silver producer in 1942 and contributed over 43 percent of the silver produced in the Western Hemisphere, compared with about 38 percent in 1941.

Hidalgo again was the leading State in Mexico in silver production, its output amounting to about 10 percent of the world output. Credit for this is due mainly to Real del Monte y Pachuca, the world's

largest silver mine.

Chihuahua, Zacatecas, and San Luis Potosí also were large producers of silver, most of which was a byproduct from the smelting of zinc-lead ores. Six large base-metal mines in Chihuahua were important producers: The American Smelting and Refining Co. (three mines), El Potosí Mining Co., the San Francisco Mines of Mexico, Ltd., and the Moctezuma Lead Co. In Zacatecas two large base-metal mines—the Fresnillo Co. and Peñoles S. A.—were credited with

most of the State's output of silver. The Fresnillo Co. produces about three times as much silver as any other base-metal mine in Mexico. In San Luis Potosí, silver from base metals is produced mainly at the mines of the American Smelting & Refining Co. at Charcas, the Kildun y Anexas at Matehuala, and the María de la Paz y Anexas at La Paz. The base-metal mine of the American Smelting & Refining Co. at Angangueo in Michoacán continued to be a large producer of silver.

During the last decade, base-metal ores in Mexico have assumed increasing importance as sources of silver, whereas the importance of silver ore has declined. In 1935, about 75 percent of the silver in the Republic was derived from silver ore, which now contributes only about 55 percent; base-metal ores have risen not quite to 45 percent.

As in the past, gold production was not outstanding in Mexico in 1942. The largest gold mine is Dos Estrellas en El Oro y Tlalpujahua, S. C. L. in Michoacán, although the silver mine Real del Monte y Pachuca surpasses it in gold output.

# CENTRAL AMERICA6

Costa Rica.—Mining in Costa Rica is virtually limited to gold mining. All producing districts are on the western slope of the mountains facing the Gulf of Nicoya. All the operations are small, the mills having a daily capacity of 5 to 50 tons of ore. Four companies mined substantial quantities of ore in 1942—the Abangarez holdings, the Compañia mine, the Juchem and Sanford operations, and the Bonanza mine (Rudin Co.). Total production for the country in 1942 approximated a value of \$500,000. This is not a large amount, but it is a very important item in the economy of this little country.

Honduras.—Some quantity of gold and silver is mined in Honduras. Only two producers are recorded: The New York & Honduras Rosario Mining Co. at San Juancito and the Cia. Minera Agua Fria, S. A. near Dolbi

S. A., near Delhi.

The Rosario mine, operating for 62 years, has a 500-ton mill and in 1941 produced 3,500,000 ounces of silver and 23,000 ounces of gold. The Agua Fria mine was opened in 1935; it has a 100-ton mill and in 1941 produced 12,000 ounces of gold and 16,000 ounces of silver. Ore

reserves are relatively small.

Nicaragua.—1942 was the sixth consecutive year in which Nicaragua has led all Central American countries in gold production. The eight important operating companies, listed in order of output, were as follows: La Luz de Los Angeles; the Neptune Gold Mining Co.; Compañia Minera La India; Impresa de Nicaragua; Compañia Minera del Javali (operating continuously for 80 years); San Juan Mines, Inc.; Compañia Minas Matagalpa; and Compañia de San Gregorio. Quartz ores are the most important sources of gold. Transportation is the major problem in prospecting for gold ores and developing them.

#### SOUTH AMERICA

Golding mining declined in a number of South American countries in 1942 because of difficulty in getting machinery and supplies from the United States, a shortage of ships for transporting ores and con-

<sup>&</sup>lt;sup>6</sup> Much that follows on Central and South America is taken from a series of articles on Gold and Silver in Latin America: Eng. and Min. Jour., vol. 143, No. 8, August 1942, pp. 75–115.

こうできるからいかのかないとはないのであるないからなっているという

centrates to United States smelters, wage competitions in certain other industries, fear of foreign capital to make investments at this time, and the uncertain attitude of the United States toward a gold policy. This decline tended to disrupt to some extent the internal economies of several of these countries by reducing the amount of foreign exchange available for imports.

Argentina.—Formerly most of the gold in Argentina came from placers along the Andes, but more recently lodes have been developed and now produce 65 to 70 percent of the total output. Production is still small. The most important minelistel Oro, in the Province of

La Rioja.

Brazil.—Although some gold is mined in nearly every State in Brazil, the major part comes from Minas Gerais. The Morro Velho, the largest producer, continued to increase its ore reserves and is now reported to have 8,000,000 tons blocked out. Progress was made also in minimizing the high temperature in this mine, the deepest in the world, by installing an extensive cooling and ventilating plant. The Morro Velho mill has a daily capacity of 1,000 tons of ore, which in

1942 averaged 11 grams of gold per ton.

Chile.—Before 1932, Chile's annual output of gold totaled only 30,000 ounces, derived largely from copper ores and concentrates. Since that date, the industry has expanded rapidly until it has reached or exceeded 300,000 ounces during at least 3 years. Lode deposits have increased in importance, and placers have declined. Much encouragement has been given small operators; as a result, thousands of gold mines have been discovered and worked since 1932. Most of the gold veins are found in the Coast Range or along the longitudinal valley running the length of the country and are genetically related to the great granodiorite intrusions so common in Chile. Generally the mines are shallow and work only the zone of secondary enrichment; the ore falls in grade in the primary zone at depth. The Provinces of Atacama and Coquimbo yield the bulk of production. In 1942 gold mining in Chile employeed about 30,000 men.

Colombia.—Gold, next to coffee, is the most important source of revenue in Colombia. It is stated that in 1942, 80,000 men were engaged in gold mining and 500,000 people derived a living from the industry in one way or another. The importance of gold in the economy of the country thus becomes very evident. The Department of Antioquia produced 60 percent of the total gold; the Intendencia

of Chocó ranked second.

Slightly more than half of the gold output in Colombia comes from placers; the rest from gold lodes. In placer operations the larger companies use dredging; the smaller ones hydraulicking. Most of the dredges are along the San Juan, Porce, Cauca, and Supia Rivers. About 52 percent of the output comes from a few large but well-equipped foreign companies; 14 percent from medium-size companies, mostly Colombian-operated; and 34 percent from small operators. Silver and platinum are important byproducts of gold mining.

Ecuador.—As in 1941, the Portovelo mine (opened in 1896) of the South American Development Co. and the Macuchi mine of the Cotopaxi Exploration Co. produced the bulk of Ecuador's output of gold and silver. No information is available on the six other com-

panies that did exploratory work in 1941.

Peru.—Peru easily takes first place among South American countries in output of silver. In 1942, about 60 percent of the output was derived from lead and copper ores. The Cerro de Pasco Copper Corporation was the largest producer and handled the ores of many smaller operators as well as its own. In output of gold, about 61 percent was supplied by gold lodes, 30 percent by base-metal ores, and 9 percent by placers. The gold-mining industry employed 9,000 of the Nation's 27,000 mining laborers and supplied 24 percent of the revenue accruing to the mining industry.

Venezuela.—In 1942, about 95 percent of Venezuela gold output came from the mines of the New Goldfields and the French Mocupia in the Callao district. Small operations declined, largely because of the attraction of diamond mining on Surukun River in the Great Savannah. Difficult transportation is a serious handicap to prospect-

ing for gold in Venezuela.

#### AFRICA

South Africa.—The objective of South Africa was to maintain gold production during 1942 at the 1941 level, but rising costs and the reluctance of the United States and Great Britain to allocate supplies and shipping space pushed output down slightly. South Africa continued to lead by a wide margin all countries in the world in gold production. Output was 14,120,617 ounces compared with 14,386,361 ounces in 1941, a decline of less than 2 percent. To produce this quantity of gold, 66,979,700 tons of ore were treated, compared with 67,255,450 tons in 1941. The tenor of the ore has been steadily declining from 0.224 ounce of gold per ton in 1938 to 0.210 ounce per ton in 1942.

#### OCEANIA

Australia.—The position of Australian gold mines was reported to be uncertain in 1942. Operators claimed that the attitude of the Government was unsatisfactory in that it was first stated that the gold industry was vital to the Commonwealth and must be continued; yet the industry had been denuded of its best men for other work or for the armed forces; and the Government had established no sound policy to serve as a basis for planning and building in the future. Production in Western Australia slumped nearly 24 percent from the 1941 output.

New Guinea.—Information on New Guinea for 1942 is meager, but it is known that some gold mines were forced to close early in the year when buildings and equipment were destroyed by the invading

Japanese army.

Tasmania.—For a number of years Tasmania has produced more than a million ounces of silver annually. Base-metal ores are the principal source, zinc-lead ores supplying over 70 percent. Base-metal ores also contribute most of the gold—zinc-lead ores 53 percent and copper ores 40 percent.

# COPPER

### By T. H. MILLER AND H. M. MEYER

#### SUMMARY OUTLINE

	Page	i il a enn e Bourk e y juan en s	Page
General summary		Domestic production—Continued.	
Salient statistics	129	Primary copper—Continued.	
Investigations of the Bureau of Mines and		Quantity and estimated recoverable con-	
Geological Survey	130		137
Reconstruction Finance Corporation lending		Refinery production	139
policy	131	Copper sulfate	141
Bonus payments	131	Secondary copper	
Labor conditions	132	Consumption	141
Consumption and distribution controls		Stocks	142
Price action	134	Prices	143
Domestic production	134	Foreign trade	145
Primary copper	134	Imports	
Smelter production		Exports	148
Mine production		World aspects of copper industry	151
Production by States and districts	136	Review by countries	155

### GENERAL SUMMARY

Copper may not have been the most critical metal in the war economy in 1942; but several authorities so termed it, and without question it was one of the top three on the list. On the whole, trends in the copper industry in 1942 were merely continuations and accentuations of those in evidence during 1941. Domestic mine and smelter production rose again in 1942, were each 13 percent above 1941, and were the largest annual amounts ever reported. Receipts of refined copper from abroad also continued to rise, and they established a new high record. Exports of copper, though above those in 1941, were again notably low as compared with most years in the twentieth century. Prices remained unchanged at ceilings fixed in 1941, but bonus payments offset the high cost of operations at some mines. Despite Government consumption-restriction orders on copper and efforts of the Government and others to encourage substitution of more abundant materials, military and essential civilian needs again could not be Consumption once more reached staggering heights, never previously attained.

Efforts of various Government agencies were directed more sharply than ever before toward increasing copper production from mines and scrap materials, toward greater imports (particularly of the higher grades of product), toward preventing consumption for all unnecessary purposes and reducing it wherever else possible, and toward confining

exports to the essential needs of our allies.

Aids in expanding the domestic output included exploratory work and drilling operations in promising areas by the Geological Survey and Bureau of Mines, liberalization of the lending policy of the Reconstruction Finance Corporation in connection with mine development, plant construction by the Defense Plant Corporation, bonus payments by the Metals Reserve Co. for production over established quotas, and priority assistance of the War Production Board to the undisturbed flow of necessary materials for productive operations.

Many of these factors are described in greater length later in this report. On the other side of the picture, reduction in unnecessary consumption was attained principally through orders issued by the War Production Board, at times in cooperation with other agencies. As a result of W. P. B. limitation orders, the use of copper has been discontinued in thousands of civilian products, and the Army, Navy, and Maritime Commission have cooperated by reducing copper requirements for many necessary items. Copper exports are also under strict control. An example of a noteworthy saving of copper is given in the report of the Communications Equipment Division of W. P. B., which states that only about 12,000 tons will be needed in the wire-communications industry for maintenance and operation of the domestic telephone and telegraph networks during 1943. estimated that an equal amount of copper in the form of scrap would be returned to the Nation's stock pile by this industry. The companies were said to have used 35,000 tons in 1942 and between 90,000 and 100,000 tons in 1941.

As a result of the conservation measures mentioned, inventories of thousands of tons of copper and copper products were frozen, and the Government arranged to purchase these stocks through the Copper Recovery Corporation, formed in May 1942. A report released in May 1943 stated that the original estimates of idle and excessive copper to be recovered ranged from 400 to 500 million pounds. Thus far, according to the report, 114,000 firms had been approached under the program, and plans were being made to reach 98,000 plumbers, building contractors, and their suppliers. A total of 197 million pounds had been allocated, of which 56 million were sold for use in unchanged form, 93½ million were allocated for remelting, 30 million were directed into the regular scrap markets, and owners were authorized to retain 17 million for essential production.

The Metals Reserve Co. and the Board of Economic Warfare provided for the purchase of available foreign copper, particularly in Western Hemisphere countries; and the Maritime Commission secured all possible shipping facilities, concentrating primarily on providing space for bringing into the country at the least all possible amounts of refined and blister copper.

と のないとうならればないないとうないという

Salient statistics of the copper industry in the United States, 1925-29 (average) and 1939-42, in short tons

	A verage (1925–29)	1939	1940	1941	1942
New copper produced—					
From domestic ores, as reported by—		1			
Mines	885, 826	728, 320	878, 086	958, 149	1,080,062
Ore produced:	300, 320	120,020	310,000	500,110	1,000,002
Copper ore	59, 505, 871	1 55,239, 098	1 69, 278, 476	1 78, 452, 504	(2)
Average yield of copper,	00, 000, 011	00,200,000	- 00, 210, 110	10, 102, 001	• • •
percent	1.44	1.25	1.20	1.15	(2)
Smelters	892, 730	712, 675		966, 072	1, 087, 991
Percent of world total	51	30	(2)	(2)	(2)
Refineries	890, 767	704, 873	927, 239	975, 408	1, 064, 792
From foreign ores, matte, etc., re-	090, 101	101,010	021, 200	210, 100	1,001,702
finery reports	317, 287	304, 642	386, 317	419, 901	349, 769
Total new refined, domestic and for-	311, 201	501,012	300, 311	110, 001	010, 100
eign	1, 208, 054	1,009,515	1, 313, 556	1, 395, 309	1, 414, 561
Secondary copper recovered from old	1, 200, 001	1,000,010	1, 510, 500	1, 550, 500	1, 111, 001
scrap only	347, 512	286, 900	333, 890	412, 699	427, 122
Copper content of copper sulfate pro-	047, 012	200, 500	000,000	112,000	721, 124
duced by refiners	4, 601	4, 868	5, 643	6, 984	8,076
Total production, new and old and	1,001	1,000	0,010	0,001	0,010
domestic and foreign	1, 560, 167	1, 301, 283	1, 653, 089	1, 814, 992	1, 849, 759
Imports (unmanufactured) <sup>3</sup>	391, 212	336, 297	491, 342	735, 545	757, 974
Refined 3	59, 236	16, 264	68, 337	346, 994	395, 039
	522, 616	427, 517	427, 650	158, 893	212, 309
Exports of metallic copper		396, 406			132, 467
Refined (ingots, bars, rods, etc.)	482, 868 307, 200	355, 500	334, 500		319, 500
Stocks at end of year	86, 100	95, 500	91, 500		84,000
Refined copper		260, 000		240,000	235, 500
Blister and materials in solution	221, 100	200,000	240,000	240,000	200, 000
Withdrawals from total supply on					
domestic account:	778, 123	714, 873	1, 008, 785	1, 641, 550	1, 670, 633
Total new copper		1, 215, 000	1, 541, 000	2, 368, 000	2, 598, 000
Total new and old copper	1, 288, 700 14, 7	1, 215, 000	11.3	11.8	2, 555, 000
Price, averagecents per pound_					
World smelter production, new copper.	1,761,000	6 2, 405, 000	(2)	(2)	(2)

1 Includes old tailings.
2 Figures not yet available.
3 Data include copper imported for immediate consumption plus material entering country under bond.
4 Total exports of copper, exclusive of ore, concentrates, composition metal, and unrefined copper. Exclusive also of "Other manufactures of copper," for which figures of quantity not recorded.
5 Exclusive of bonus payments of the Metals Reserve Co.

Although our total supplies of copper failed by a substantial margin to fill our own total demands, it was imperative that consideration be given to the essential requirements of our Allies; according to Lend-Lease authorities, 7.2 percent of our total new supply (production plus imports) for 1942 was exported.

Another important step in balancing supplies and requirements was the increasing use of substitutes. In this connection, Lt. Gen. Brehon B. Somervell, commanding the Army Service Forces, recently said:

In the 2 years 1942-43 we shall save 400,000,000 pounds of copper, probably our most precious metal today, by using steel in cartridge cases instead of brass. Nearly 50 producers now are making steel shell cases. In addition, by substitution and other engineering changes, we shall save 75,000,000 pounds of copper

Because more copper was available for use than ever before, because of the successful efforts to reduce consumption of copper in many ways through curtailing uses and substitution, and because it was almost impossible to accept the fact that even modern warfare could require such enormous quantities of this metal, some observers felt that the copper problems had been solved. In contradiction of this attitude H.O. King, chief of the Copper Branch, War Production Board, said early in 1943:

Recent statements quoted in the press have conveyed the impression that the supply of copper is adequate to meet all military and essential civilian requirements. Widespread acceptance of such statements would constitute a threat to our entire war production program. The supply of copper is not adequate and never will be while this war is on. \* \* \*

As we got deeper into war, the Office of War Information determined that it was inadvisable to release information on many raw materials, and both trade and Government statistics were involved. Publication of Bureau of Mines monthly copper mine figures was discontinued following the statement for January 1942. Trade data on smelter and refinery production and stocks, and fabricators' figures on consumption and stocks were not revealed after May. Domestic sales data were

not released after June.

In January 1942 the Copper and Zinc Branch of the War Production Board was separated into two branches, and in February, Harry O. King was named to head the Copper Branch. King had previously been in Government service as the division administrator of National Recovery Administration, from which he resigned to become managing director of the Copper Code Authority. A Copper Producers Advisory Committee was formed later, with King as its chairman and the following members from industry: K. C. Brownell, vice president, American Smelting & Refining Co.; Robert E. Dwyer, vice president, Anaconda Copper Mining Co.; Carl T. Ulrich, vice president, Kennecott Copper Corporation; J. F. McClelland, vice president, Phelps Dodge Corporation; A. J. McNab, vice president, Magma Copper Co.; B. N. Zimmer, vice president, American Metal Co.; and A. E. Petermann, vice president, Calumet & Hecla Consolidated Copper Co. Early in 1943 a Combined Copper Committee was set up by the Combined Production and Resources Board and the Combined Raw Materials Board to assemble and review data on supplies and requirements of the United States, the United Kingdom, and Canada in order that available metal be most efficiently utilized. King was made chairman of this committee.

CONTRACTOR OF THE PROPERTY OF

# INVESTIGATIONS OF THE BUREAU OF MINES AND GEOLOGICAL SURVEY

Prospecting for copper ores was begun in July 1942, when allotments for exploration projects were made from funds appropriated to the Bureau of Mines for investigation of critical and essential minerals. At the close of the calendar year 1942, 12 exploration projects had been established, involving diamond drilling at 9 deposits, surface trenching at 2, and underground sampling at 1. One project was

completed in 1942.

Among results of the prospecting in 1942 were: (1) The establishment of additional reserves of indicated ore at the Elizabeth mine of the Vermont Copper Co., Orange County, Vt., amounting to 300,000 tons averaging over 2 percent copper. Production is expected to begin in March 1943; (2) the discovery of about 75,000 tons of indicated ore containing 2.06 percent copper and 0.3 percent cobalt at the Uncle Sam mine, Blackbird district, Lemhi County, Idaho; (3) the finding of some ore at depth in the Christmas mine, Gila County, Ariz.

In the laboratory, favorable tests were made: (1) To separate tungsten from copper minerals at the Empire mine, Custer County, Idaho; (2) to float selectively copper and cobalt minerals at the Uncle Sam mine, Lemhi County, Idaho; (3) to treat ores from the Hidden Treasure

mine, Missoula County, Mont.

COPPER 131

THE REPORT OF THE PARTY OF THE

During the calendar year 1943 the Bureau of Mines plans to continue prospecting at the Elizabeth mine, Uncle Sam mine, and Christmas mine and to explore additional deposits when investigations now in progress are completed. The Bureau also intends to investigate

the possibilities for re-treating mill tailings at several plants.

In the latter half of 1942 the Geological Survey greatly expanded its studies of copper deposits, in accordance with its program of investigating deposits of minerals currently needed for war production. Although emphasis was focused on detailed studies in minor districts that offer favorable possibilities for increased production, many brief examinations of individual copper deposits also were made during the year, often at the request of other Government agencies. Geologic investigations were made of copper deposits in the continental United States, Alaska, and several Latin American republics.

At the end of 1942 investigations in the United States were in progress in the Elizabeth mine, Vermont; Michigan; Pastura, N. Mex.; Christmas mine and Old Hat district, Arizona; the Penn mine, California; Glacier Peak, Wash.; Mackay, Idaho; and the Southeastern States. In several of these projects, Survey geologists were collaborating with Bureau of Mines engineers on exploration projects.

In Alaska during the summer of 1942, the Geological Survey investigated nickel-copper deposits at Spirit Mountain (Copper River region), at Mirror Harbor (Chichagof Island), and at Bohemia Basin (Yakobi Island); copper-molybdenum deposits at Orange Hill (Copper River region); iron-copper deposits of the Mount Andrew-Mamie area and the Poorman area (Prince of Wales Island); and copper-palladium deposits at the Salt Chuck mine. Reports on several earlier investigations in Alaska <sup>1</sup> were published during 1942.

In 1942 Survey geologists investigated copper deposits in Cuba and Haiti under the auspices of the Department of State and in Colombia and Central America under the auspices of the Board of Economic

Warfare.

#### RECONSTRUCTION FINANCE CORPORATION LENDING POLICY

The lending policy of the Reconstruction Finance Corporation was liberalized in March to permit the owner or lessee of a mining property to borrow amounts not exceeding \$20,000 to defray costs of developing small ore bodies containing strategic and critical metals. The loans were to be obtainable out of R. F. C. funds, repayable out of proceeds from operations; if the initial development showed favorable results, additional loans up to another \$20,000 were to be had for further development.

BONUS PAYMENTS

Government action regarding the payment of bonuses to individual producers for production of copper over established quotas, whereby the payments were made by the Metals Reserve Co. and the quotas were assigned by the War Production Board and the Office of Price Administration, was discussed in the Copper chapter of Minerals

<sup>1</sup> Reed, J. C., and Dorr, J. V. N., II, Nickel Deposits of Bohemia Basin and Vicinity, Yakobi Island, Alaska: Geol. Survey Bull. 931-F, 1942, 34 pp.
Pecora, W. T., Nickel-Copper Deposits on the West Coast of Chichagof Island, Alaska: Geol. Survey Bull. 936-I, 1942, 23 pp.
Reed, J. C., and Gates, G. O., Nickel-Copper Deposit of Snipe Bay, Baranof Island, Alaska: Geol. Survey Bull. 936-M, 1942, 10 pp.
Reed, J. C., Nickel-Copper Deposit at Funter Bay, Admiralty Island, Alaska: Geol. Survey Bull. 936-O, 1942, 13 pp.

Yearbook, 1941. The quotas assigned were said to be so high that there was little chance that larger producers could produce enough copper to benefit. Small, high-cost, and new producers were the immediate beneficiaries. At the same time, the plan was sufficiently flexible so that at any time quotas could be lowered to give greater aid, without affecting the price of copper to consumers. Moreover, the quotas were established by mines or groups of mines rather than by companies, to avoid any possibility that expenditures for expansion of one property might be deterred by uncertainties as to future production from one mine or group of mines of the same company. Many quotas were revised downward during the year. An increasing number of copper quotas were lowered in the last month of the year and into This action was taken largely to permit copper companies to absorb the additional costs of mining caused by rather general wage increases late in the year. In recognition of the possibility of greater production gained by having an established, satisfactory price over an extended period, the Government in January 1943 extended the premium plan to July 31, 1945. The plan was amended May 1, 1943, to make possible additional premiums for mines that produced less than 2,000 tons of copper in 1942 and which required increased revenue to obtain maximum production. Individual mines were to be studied independently and special premiums to be paid for output over special quotas established. The Metals Reserve Co. announced that royalty payments on production entitled to premium payments would be paid on ceiling prices unless the lease specifically instructed otherwise, as it was not the intent of the order to have anyone other than the actual operator participate in the plan. Royalties paid by domestic mine operators for copper, lead, and zinc ores mined from leased properties were frozen by the Office of Price Administration on April 1, 1943. at rates in effect on December 31, 1942.

# LABOR CONDITIONS

The labor situation at mines, mills, smelters, and refineries got progressively worse as the year advanced and reached a low point about August. At that time the War Labor Board was considering action in a large number of nonferrous mine cases which it had promised the miners to expedite. Local draft boards were requested to see that the mining program was not scotched by Army manpower require-The International Union of Mine, Mill and Smelter Workers reported that 3,000 men would be required to raise operations to full Later in the month the War Manpower Commission subjected migrations of lumber and copper workers in 12 Western States (termed a "critical labor area") to United States control. The States were Arizona, California, Colorado, Idaho, Montana, Nevada, New Mexico, Oregon, Texas, Utah, Washington, and Wyoming. In this area workers could not switch jobs (except under certain specified conditions) or employers release workers without first obtaining certificates of separation from the United States Employment Service. Gold mining was virtually stopped in the hope of inducing workers in those mines to accept employment in strategic metal mines, and the Government furloughed 4,000 men from the Army provided they

COPPER 133

entered the strategic metal mines, particularly copper mines. The mines were benefited, at least temporarily, by a greater number of employees. Many of the recommended wage increases were accepted by the War Labor Board and subsequently approved by the Director of Economic Stabilization. The increases granted took up only part of the slack between wages in the mining industry and in others, such as airplane factories, shipyards, etc., and the urge to leave mining communities continued to be a deterrent factor in the labor situation.

#### CONSUMPTION AND DISTRIBUTION CONTROLS

Copper, copper-base alloys, and copper scrap were under complete priority control before the beginning of 1942. The War Production Board issued amendments and revisions to the control orders from time to time throughout 1942. These were directed mostly toward increasing the restrictions on uses. The supply situation became so tight by September that the Army and Navy and the Maritime Commission agreed to rigid restrictions that confined copper consumption to vital war uses. The Production Requirements Plan (PRP) was put into operation in the third quarter of 1942 (it was partly effective beginning the first quarter); its purpose was to provide stricter controls on the distribution of scarce materials. With few exceptions it applied to all concerns using metal valued at \$5,000 during a calendar Manufacturers were asked to estimate their requirements for 3 months in advance. The plan was closely tied in with end-use allocation classification. An intricate system of numerical symbols was provided to identify the ultimate use to which the raw material was to be put. This plan, it was announced in November, was scheduled to give way to the Controlled Materials Plan (CMP) in part in the second quarter of 1943 for aluminum, copper, and carbon and alloy steel, "the three most basic and critical materials," and to be completely superseded by CMP for these products by July 1943. Under PRP each firm, large or small, prime contractor or subcontractor, submitted its own requirements to the War Production Board for approval and received an individual authorization to obtain materials. Under CMP, prime contractors were to prepare and submit a breakdown of all materials required for the approved end-products on which they are working. The break-down was to comprise a "bill of materials" specifying not only what materials were required, but when they must be received to carry out the authorized program. The bills of materials were to include controlled materials required by the prime contractors and their subcontractors and their suppliers and also other scarce materials listed in the outline of the plan. bills of materials from prime contractors were to be assembled by claimant agencies and presented to the War Production Board Requirements Committee and to the respective Controlled Materials Branches, which were to make the necessary adjustments to bring the whole program into balance with available supplies. The original claimant agencies included the Army, Navy, Maritime Commission, Aircraft Scheduling Unit, Office of Lend-Lease Administration, Board of Economic Warfare, and Office of Civilian Supply, but this list was promptly expanded.

### PRICE ACTION

Ceiling prices of the Office of Price Administration for electrolytic and casting copper were discussed in the chapter on Copper in Minerals Yearbook, 1941. The principal price action on copper in 1942 (which, however, did not affect the price to consumers) was the establishment of bonus payments for overquota production, which already have been discussed under that heading. Ceilings for less than carlot shipments were revised in 1942; prices for copper alloy and scrap items not already covered were established by the General Maximum Price Regulation in May 1942 at the levels prevailing in March (many of which were changed by subsequent orders), and the prices to be paid by the Government for copper and copper-base alloy products in inventories frozen by various limitation and conservation orders were selected. Establishment of specifications and cents-perpound prices for 16 new grades of copper scrap and copper-alloy scrap, effective March 22, 1943, brought under specific prices the entire field of such material when sold to consumers. Ceiling prices on scrap items are discussed in the chapter on Secondary Metals—Nonferrous.

#### DOMESTIC PRODUCTION

The second design of the secon

Statistics on copper production may be compiled upon a mine, smelter, or refinery basis. Mine data are most accurate for showing the geographic distribution of production; smelter figures are better for showing the actual recovery of metal and fairly accurate for showing the source of production; and refinery statistics give precise information regarding metal recovery but indicate only in a general way the source of crude materials treated. The chapter on Copper in Mineral Resources of United States, 1930, part 1, discusses the differences among the three sets of figures.

Copper produced from domestic ores, as reported by mines, smelters, and refineries, 1938-42, in short tons

	Year	Mine	Smelter	Refinery
1938 1939 1940		557, 763 728, 320 878, 086	562, 328 712, 675 909, 084	552, 574 704, 873 927, 239
1941 1942		958, 149 1, 080, 062	966, 072 1, 087, 991	975, 408 1, 064, 792

#### PRIMARY COPPER

Smelter production.—The recovery of copper by United States smelters from ores of domestic origin totaled 1,087,991 short tons in 1942—a 13-percent increase over 1941. Domestic smelter output constituted 51 percent of the world production during 1925–29. The proportion dropped sharply in the succeeding years until 1934, when it was only 17 percent. It rose to 32 percent in 1936 and from then until 1939 never fell below 25 percent, fluctuating between the two figures. The proportion was believed to be between 31 and 35 percent in 1940 to 1942 and to be at the top of this range in the latest year.

The figures for smelter production are based upon confidential returns from all smelters handling copper-bearing materials produced in the United States. For Michigan the sum of furnace-refined copper

135 COPPER

はいって、これが、 100mm を 100mm を 100mm でしまっている。 100mm では、 100mm でしまっている。 100mm でしまっている。 100mm でしまっている。 100mm でしまっている。

and copper cast into anodes for electrolytic refining is included. figures for blister represent the fine-copper content. Some casting and electrolytic copper produced direct from ore or matte is included in the smelter production. Metallic and cement copper recovered by leaching is included in smelter production.

The precise quantity, in pounds, of copper produced by smelters in the United States and its value are shown by years for 1845-1930 in the Copper chapter of Mineral Resources of the United States, 1930,

part 1.

Copper produced in the United States from domestic ores, 1938-42, by States [Smelter output, in short tons fine]

State	1938	1939	1940	1941	1942
Alaska	16,746	152	64	95	33
Arizona		262, 706	287, 267	328, 550	388, 394
Dalifornia		4, 246	6, 546	4, 015	1,019
Coloredo	15, 282	12,774	13, 186	6, 483	1, 249
Georgia	(1)		13		2 2 4 4 7 3 1 5
daho	2.806	2, 316	3,690	3, 551	3, 889
Michigan	37,641	44, 701	45, 743	46, 752	47, 470
Vissourii	313	510	819	773	2,658
Montana	78, 125	101,756	129, 071	128, 712	140, 465
Vevada	46,828	64, 422	78, 621	80, 518	83, 434
New Mexico	21,956	37,042	70, 484	73, 848	79, 598
North Carolina	(2)	(2)	(2)	(2)	(3)
)regon	44	48	101	84	113
Pennsylvaniaouth Carolina	(2)	(2) (1)	(2)	(2)	(1)
outh Carolina	4	(1)			1
South Dakota			. 6		
Pennessee	(2)	(2)	(²) 33	(3)	(3)
Pexas	18	163, 059	248, 732	970 647	104 317, 717
Jtah Virginia	114, 938	(1)	240, 102	270, 647	911, 111
Virginia Vashington	6, 247	8,378	10, 511	8, 667	8, 525
Washington		0,010	10, 011	0,001	0,020
Jndistributed	10,342	10, 532	14, 195	13, 366	13, 321
) Haiswing wear	10,012	10,002	11,100		10,011
	562, 328	712,675	909,084	966, 072	1,087,991

Copper produced (smelter output) in the United States, 1938-42, and total, 1845-1942 [Values rounded]

		Year	Short tons	Value
1938			562, 328 712, 675 909, 084 966, 072 1, 087, 991	\$110, 216, 000 148, 236, 000 205, 453, 000 227, 993, 000 1 256, 766, 000
Total, 1845-19	42		29, 552, 541	8, 736, 779, 000

<sup>1</sup> Excludes bonus payments of Metals Reserve Co.

Mine production.—The figures for mine production are based upon reports supplied to the Bureau of Mines by all domestic mines that produce copper. Details of the method of collecting the statistics and reasons for the discrepancy between mine-, smelter-, and refinery-production figures are given in the Copper chapter of Mineral Resources of the United States, 1930, part 1.

Mine production is more accurate than either refinery or smelter production for showing the distribution of domestic output by States and districts. It also indicates the production by calendar years more

Less than 1 ton.
Included under "Undistributed"; Bureau of Mines not at liberty to publish figures.

exactly, because additional time is required for smelting and refining. Mine production in 1942 was 1,080,062 tons—an increase of 13 percent over that in 1941 and 22 percent above the average for 1925-29.

Production by States and districts.—The following tables show mine and smelter production by States for 1941 and 1942 and mine output by districts for 1938-42. In 1942 Arizona, Utah, and Montana led in production with 78 percent of the smelter total compared with 75 percent in 1941; adding the output of Nevada, New Mexico, and Michigan to the foregoing brings the proportions to 97 percent of the total for the country compared with 96 percent in 1941. supplied 36 percent compared with 29 percent for Utah and 13 percent Montana's share of the total was unchanged from for Montana. 1941, but the other two States showed gains. The three other most important copper-producing States (Nevada, New Mexico, and Michigan) represented smaller proportions of the country's total in 1942, although all produced more copper than in 1941. Among other States. there were sharp drops in output for Colorado and California. These declines were due to replacement of production of copper-iron-silvergold ore in favor of zinc-lead ore at the Eagle mine of the New Jersey Zinc Co. in Colorado and closing of the Walker mine in Plumas County, Calif., which left that State without an important copper producer. Comparison of present production with that of the past century shows that Utah's share of the country's total is rising sharply, whereas Arizona's is becoming static at somewhat above the earlier period. Michigan and Montana are dropping markedly, while New Mexico and Nevada are advancing.

Copper produced in the United States, according to smelter and mine returns, by States, 1941-42 and 1845-1942, in short tons

	19	41	1942			1845–1942 smelter output		
State			Smelte	r returns				
	Smelter returns	Mine returns	Percent of total	Quantity	Mine returns	Total quantity	Percent of total	
Alaska	95	72	(1)	33	22	676, 816	2. 2	
Arizona	328, 550	326, 317	35. 70	388, 394	393, 387	9, 802, 882	33. 1	
California	4,015	3, 943	.09	1,019	1,058	575, 487	1.9	
Colorado	6, 483	6, 748	. 11	1, 249	1, 102	272, 764	.9	
Georgia Idaho		3, 621		3, 889		(2)	(2)	
Michigan	3, 551 46, 752	3, 621 46, 440	. 36 4. 36	3, 889 47, 470	3, 430 45, 679	95, 380 4, 684, 855	.3 15.8	
Missouri	773	1, 400	. 25	2, 658	1, 300	(2)	(2)	
Montana	128, 712	128, 036	12. 91	140, 465	141, 194	6, 223, 222	21.0	
Nevada		78, 911	7. 67	83, 434	83, 663	1, 536, 911	5. 2	
New Mexico	73, 848	73, 478	7. 32	79, 598	80, 100	1, 089, 901	3. 6	
North Carolina	(3)	(3)	(3)	(3)	(3)	(2)	(2)	
Oregon	`´ 84	83	`.01	113	103	ìí, 648	.0	
Pennsylvania	(3)	(3) (4)	(3) (1)	(3)	(3) (4)	(2)	(2) (2)	
South Carolina		(4)	(1)	1	(4)	(3)	(2)	
South Dakota					1	(2)	(2)	
Tennessee	(3)	(3)	(3)	(3)	(3)	§ 259, 508	ৣ⁵.8	
Texas	270, 647	266, 838	.01	104	99	(2)	(2)	
Utah Virginia	270, 047	200, 838	29. 20	317, 717	306, 691 28	3, 985, 455	13. 4 (2)	
Washington	8, 667	8, 686	. 78	. 8, 525	8, 030	(2) 56, 801	. 1	
Wyoming	3, 007	3,000	(1). 18	1 0,020	0,000	15, 870	.0	
Undistributed	13, 366	13, 566	í. 23	13, 321	14, 175	6 265, 041	6.9	
	966, 072	958, 149	100.00	1, 087, 991	1, 080, 062	29, 552, 541	100.0	

<sup>1</sup> Less than 0.01 percent. 2 Included under "Undistributed"; figures not separately recorded.
2 Included under "Undistributed"; Bureau of Mines not at liberty to publish figures. 4 Less than 1 ton.
4 Approximate production through 1928. Figures for 1929–42 confidential and included under "Undistributed". 6 Includes Tennessee for 1929–42.

In 1942 the Bingham (Utah) district experienced no difficulty in maintaining its lead among the copper-producing districts of the country for the seventh consecutive year; its output was 117 percent higher than that of its nearest competitor, the Butte (Mont.) district. For 7 years the Butte district ranked second in production, and its total production from the beginning of operations is far above that of any other district in the country. Following the Globe-Miami district, Ariz., which has ranked third for a number of years, is a group of districts that frequently changes place in importance as copper producers.

Details of mine production, by districts and companies, in 1942 are available in the chapters of this volume dealing with the production

of gold, silver, copper, lead, and zinc in the various States.

Mine production of copper in the principal districts of the United States, 1938-42, in terms of recovered copper, in short tons

District or region	State	1938	1939	1940	1941	1942
Bingham	Utah	106, 049	167, 856	228, 505	264, 705	304, 68
Summit Valley (Butte)	Montana	76, 855	97, 266	125, 442	127, 431	140, 349
Globe-Miami Ely (Robinson)	Arizona	44, 528	62, 400	70, 406	82, 419	94, 26
Ely (Robinson)	Nevada	38, 501	51, 590	63, 840	67, 171	75, 06
Central (including Santa Rita). Ajo	New Mexico	16, 557	42, 344	64, 991	67, 727	72, 72
Aio	Arizona	43, 180	49,871	51, 566	65,880	66, 64
Copper Mountain (Morenci).	do	11, 148	15,878	13, 503	13,879	60, 350
Bisbee (Warren)	do	47, 518	54, 617	55, 254	56, 592	53, 278
Ray (Mineral Creek)	ldo	15,029	21, 583	31,729	42,400	50, 362
Lake Superior	Michigan	46,743	43, 985	45, 198	46, 440	45, 67
rome district).	Arizona	29, 457	38, 203	38, 201	43, 701	44, 94
Pioneer Chelan Lake Cope Lordsburg	do	17, 167	17,958	18, 450	19, 121 8, 365	20, 702
Chelan Lake	Washington	5, 931	8,786	9, 288	8,365	7, 95
Cone	Nevada	6, 563	14,065	13, 542	10,756	7,07
Lordshurg	New Mexico	3, 173	3, 184	3, 278	3,734	3, 35
Coeur d'Alene region Tintic San Juan Mountains	Idaho	1,883	2,068	2,680	2,979	2, 99
Tintic	Utah	1,177	1,413	1, 295	1,042	85
Son Tuon Mountains	Colorado	1,819	981	1, 209	705	53
Red Cliff (Bettle Mountain)	do	12,013	11,921	10, 552	5, 609	32
Onhir	Utah	437	2,070	1,095	204	20
Red Cliff (Battle Mountain) Ophir Bunker Hill	Arizona	1,626	246	8	11	2
Diumes County	Colifornia	602	4,029	5, 293		
Plumas County San Pedro	New Marico	44	336	1, 394	719	
Copper River 2	Alaska	8 14, 549	(4)	(1)	(4)	(4)
Swain County 2	North Carolina		(4) (5) (6)	( <del>1</del> ) ( <del>5</del> )	(4) (5) (8) (5)	74
Lebanon (Cornwall mine)	Donneylyonia	\ \	- X	) N	- X	78
renamen (Cornwan mme)	Tennessee	(5) (5)	- X	(5)	) <sub>4</sub>	Ж
Ducktown 2	Termessee	0	(7)	(2)	(9)	(3)

Districts producing 1,000 short tons or more in any year of the period 1938-42. Not listed in order of output.

Includes a small quantity produced elsewhere in Alaska.

Quantity and estimated recoverable content of copper-bearing ores .-The following tables list the quantity and estimated recoverable copper content of the ore produced by mines in the United States in 1941; figures for 1942 are not yet available. Of the total copper produced from copper ores in the United States in 1941, 85 percent was obtained from ores concentrated before smelting and 10 percent from directsmelting ores; in addition, copper was recovered from 3,785,654 tons of copper ore treated by straight leaching. The percentages for 1941 compare with 84 percent obtained from concentrated ore and 11 percent from direct-smelting ores in 1940. In 1940, 3,198,904 tons of copper ore were treated by straight leaching.

Close agreement between the output as reported by smelters and the recoverable quantity as reported by mines indicates that the estimated

Bureau of Mines not at liberty to publish figures.

recoverable tenor is close to the actual recovery. Classification of some of the complex western ores is difficult and more or less arbitrary. "Copper ores" include not only those that contain 2.5 percent or more copper but also those that contain less than this percentage if they are valuable chiefly for copper. Mines report considerable copper from ores mined primarily for other metals. These include siliceous gold and silver ores, lead and zinc ores, and pyritic ores.

Copper ore, old tailings, etc., sold or treated in the United States in 1941, with copper, gold, and silver content in terms of recovered metals

State	Ore, old tail- ings, etc.,			Gold pro-	Silver pro-	Value of gold and	
	sold or treated (short tons)	Pounds	Percent	duced (fine ounces)	duced (fine ounces)	silver per ton of ore	
Alaska	144	20,876	7. 25	31	128	\$8, 17	
Arizona	24, 153, 483	1 613, 096, 452	1.27	142, 498	5,006,374	.35	
California	292, 232	7, 418, 100	1.27	12,038	179, 744	1.88	
Colorado	207, 678	11, 479, 396	2.76	25, 187	4, 306, 343	18, 99	
Idaho	7,979	687, 128	4.31	696	43, 851	6.96	
Michigan	4, 282, 448	92,880,000	1.08		60, 796	2.59	
Montana	3, 791, 202	1 244, 015, 387	3. 22	13,871	6, 142, 250	1.28	
Nevada	6,850,444	156, 649, 800	1.14	65, 510	259, 686	. 36	
New Mexico	6, 975, 682	1127, 896, 610	. 92	8,908	242, 834	. 07	
Oregon	629	48,000	3.82	10	2, 220	3.07	
Texas	58	3,000	2.59		22	.28	
Utah	30, 444, 402	1 513, 251, 387	.84	243, 953	2, 285, 377	. 33	
Washington	694, 565	17, 313, 000	1. 25	46,034	202, 091	2.53	
Wyoming	42	7, 902	9.41	2	30	2.17	
Eastern States	751, 516	<sup>3</sup> 27, 130, 735		324	44, 205		
불명 시간 된 시간 생님	78, 452, 504	3 1,811,897,773	1.15	559,062	18, 775, 951	.42	

<sup>&</sup>lt;sup>1</sup> Excludes copper recovered from mine-water precipitates as follows: Arizona, 34,323,752; Montana, 5,503,585; New Mexico, 16,818,294; and Utah, 13,418,668 pounds.

<sup>2</sup> Calculated only on ore that yielded silver.

Copper ore, old tailings, etc., concentrated in the United States in 1941, with content in terms of recovered copper

State	Ore, old tailings, etc., concentrated (short tons)	Concentrates produced (short tons)	Copper pro- duced (pounds)	Copper from ore, etc. (per- cent)
Alaska Arizona California Colorado Idaho Michigan Montana Nevada New Mexico Oregon Utaho Washington Eastern States	4, 624 3, 906 4, 282, 448 3, 790, 183 6, 825, 565 6, 901, 193 500 30, 432, 336	20 938, 095 14, 934 476 70, 550 509, 374 267, 234 222, 411 72 789, 305 372, 200 2, 921, 590	13, 932 2 374, 509, 382 7, 298, 500 192, 000 178, 814 92, 880, 000 243, 893, 505 147, 030, 600 125, 266, 413 24, 000 512, 546, 313 17, 118, 128 4 23, 834, 000 1, 544, 785, 579	6.9 1.0 1.2 2.0 2.2 1.0 3.2 1.0 9 2.4 .8 1.2

<sup>3</sup> Copper from magnetite-pyrite-chalcopyrite ore from Pennsylvania included with that from copper ore.

In addition, 3,785,654 tons were treated by straight leaching.
 In addition, 84,127,150 pounds of copper were recovered by straight leaching.
 Includes concentrates from magnetite-pyrite-chalcopyrite ore from Pennsylvania.
 Includes copper from magnetite-pyrite-chalcopyrite ore from Pennsylvania.

できる 一般 あっちょう こうしゃこ

Copper ore, old tailings, etc., smelted in the United States in 1941, with content in terms of recovered copper, and copper produced from all sources, in terms of recovered copper

	Ore, old	Ore, old tailings, etc., smelted				
State	Short tons	Copper pro- duced (pounds)	Percent of copper	all sources, including old slags, smelter cleanings, and precipitates (pounds)		
Alaska	203, 054 4, 073	6, 944 154, 459, 920 119, 600 11, 287, 396 508, 314	7.89 4.39 7.83 2.78 6.24	144, 000 1 652, 634, 000 7, 886, 000 13, 496, 000 2 7, 242, 000 92, 880, 000		
Missouri Montana Nevada New Mexico Oregon Texas Utah Washington Wyoming Eastern States	1, 019 24, 879 74, 489 129 58 12, 066 628	121, 882 9, 619, 200 2, 630, 197 24, 000 3, 000 705, 082 194, 872 7, 902 3, 296, 735	5. 98 19. 33 1. 77 9. 30 2. 59 2. 92 15. 52 9. 41 3. 10	2, 800, 000 1 256, 072, 000 1 57, 822, 000 1 146, 956, 000 1 22, 000 1 533, 676, 000 17, 372, 000 27, 132, 000 27, 132, 000		
	2, 135, 138	182, 985, 044	4, 29	1, 916, 298, 000		

Copper ores produced in the United States, 1937-41, and average yield in copper, gold, and silver

	Smelting	ores 1	Concentrati	ng ores 1		•	<b>Fotal</b>	**	
Year	Short tons	Yield in cop- per (per- cent)	Short tons	Yield in cop- per (per- cent)	Short tons 1	Yield in cop- per (per- cent)		Yield per ton in silver (ounce)	Value per ton in gold and silver
1937 1938 1939 1940 1941	<sup>2</sup> 2, 763, 184 <sup>2</sup> 2, 028, 000 2, 396, 155 2, 179, 060 2, 135, 138	4.30 4.49 4.61 4.33 4.29	2 58, 737, 922 2 34, 374, 026 50, 710, 026 63, 900, 512 72, 531, 712	1.15 1.17 1.09 1.10 1.06	2 61, 513, 148 2 37, 794, 938 55, 239, 098 69, 278, 476 78, 452, 504	1, 29 1, 34 1, 25 1, 20 1, 15	0.0081 .0090 .0085 .0078 .0071	0.327 .414 .333 .300 .239	\$0. 53 . 58 . 52 . 48 . 42

### REFINERY PRODUCTION

The refinery output of copper in the United States in 1942 was made by 11 plants; 8 of these employed the electrolytic method, 2 the furnace process on Lake Superior copper, and 1 the furnace process on western ores.

There are five large electrolytic refineries on the Atlantic seaboard, three Lake refineries on the Great Lakes, and three electrolytic refineries west of the Great Lakes—one at Great Falls, Mont.; one at Tacoma, Wash.; and one at El Paso, Tex. In 1942, fire-refined copper was produced for the first time at the Hurley plant of the Kennecott Copper Corporation. Of the above plants, the Lake refinery of the Quincy Mining Co. has been idle since 1933.

In addition to the foregoing plants, that at Inspiration, Ariz., is equipped to make electrolytically refined copper direct from the liquors obtained from leaching; this copper is shipped as cathodes to other refineries, where it is melted and cast into merchant shapes.

Considerable copper was recovered from mine-water precipitates.
 Mostly recovered from ores classed as dry and siliceous silver ore and zinc-lead ore.

Includes old tailings, etc.
 Exclusive of Alaska, figures for which Bureau of Mines not at liberty to publish.

The 13 plants indicated constitute what commonly are termed "regular refineries." Of these plants, 9 employ the electrolytic process and 4 the furnace process. The Phelps Dodge Refining Corporation plant at El Paso used both methods in 1942. The electrolytic plants have a rated capacity of 1,547,000 tons of refined copper a year. As they produced 1,390,000 tons in 1942, this part of the industry was operated at 90 percent of capacity.

The following tables show the production of refined copper at regular refining plants, classified according to source, grade, and form in which cast.

얼마를 다시하는 것은 이 이번에 사람

Primary and secondary copper produced by regular refining plants in the United States and imported, 1938-42, in short tons

	1938	1939	1940	1941	1942
Primary: Domestic: 1					
Electrolytic <sup>2</sup>	516, 488 36, 011 75	662, 409 42, 464	883, 610 43, 629	929, 711 45, 697	963, 177 46, 523 55, 092
Foreign: 1	552, 574	704, 873	927, 239	975, 408	1, 064, 792
Electrolytic Casting and best select	239, 818 24	304, 642	386, 317	419, 901	343, 834 5, 935
Refinery production, new copper Imports, refined copper 3	792, 416 1, 801	1, 009, 515 16, 264	1, 313, 556 68, 337	1, 395, 309 346, 994	1, 414, 561 395, 039
Total new refined copper made avail- able	794, 217	1, 025, 779	1, 381, 893	1, 742, 303	1, 809, 600
Secondary: Electrolytic 4 Casting	92, 542	116, 613	117, 669	95, 437 4, 238	83, 079 2, 064
	92, 542	116, 613	117, 669	99, 675	85, 143
Grand total	886, 759	1, 142, 392	1, 499, 562	1, 841, 978	1, 894, 743

The separation of refined copper into metal of domestic and foreign origin is only approximate, as accurate separation at this stage of manufacture is not possible.
 Some copper from Michigan is electrolytically refined at eastern refineries and is included as electrolytic

Some copper from Michigan is electrolytically refined at eastern refineries and is included as electrolytic copper.
 Data include copper imported for immediate consumption plus material entering country under bond.
 Includes some secondary Lake copper.

Copper cast in forms in the United States, 1941-42

	Form	194	1	194	2
		Short tons	Percent	Short tons	Percent
Wire bars		 736, 000 300, 500	49. 23 20. 10	582, 000 464, 500	38. 81 30. 98
CakesIngots		 191, 500 128, 500	12.81 8.60	119, 500 219, 500	7. 97 14. 64
Other forms		 1,495,000	9. 26	114,000	7.60

In addition to the regular refineries, numerous plants throughout the country operate on scrap exclusively, producing metallic copper and a great variety of alloys. The output of these plants is not included in the statements of refined-copper production in the preceding tables but is included in the following statement of secondary-copper production. COPPER 141

THE PARTY OF THE P

Copper sulfate.—The production of hydrous copper sulfate or bluestone by copper refineries in the United States was 31,704 short tons having a copper content of 8,076 tons in 1942 compared with 27,417 tons having a copper content of 6,984 tons in 1941.

The output of copper sulfate by plants other than the regular primary refineries totaled 72,411 tons with a reported copper content of 18,390 tons in 1942 compared with 58,072 tons containing 14,684

tons of copper in 1941.

Copper chemicals, including copper sulfate, were placed under allocation control in an order effective October 1, 1942. The Office of Price Administration set the ceiling price for copper sulfate at \$5 per 100 pounds, effective April 3, 1943, for sales by manufacturers and May 3 for sales by others. Previously the price had been \$5.15 in the East and as high as \$5.50 in the West. In May the order was amended to permit an increase to \$5.15 for deliveries in the West. In an article on insecticide chemical requirements for war food supplies McBride 2 stated that over 200,000,000 pounds of copper chemicals, principally copper sulfate, are wanted for military use, for export, for other industries, and for insecticides. Availability of scrap, he said, would determine the size of production. In 1939 51,122,000 pounds of copper sulfate were used for agricultural purposes, and in the fiscal year ended September 30, 1942, 79,539,000 pounds were so used; 86,000,000 pounds were estimated as requirements for this purpose in 1943.

### SECONDARY COPPER

Secondary copper includes material recovered from remelting old copper and copper scrap and from the treatment of copper alloys or alloys treated without separation of the copper. The following table summarizes the production of secondary copper during 1938–42. Further details appear in the chapter on Secondary Metals—Nonferrous.

			in short tons

			- Z 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1 -		
	1938	1939	1940	1941	1942
Copper recovered as unalloyed copper Copper recovered in alloys	192, 400 167, 400	151, 370 1 348, 330	170, 839 1 361, 207	135, 869 1 590, 527	114, 647 1 813, 108
Total secondary copper	359, 800	499, 700	532, 046	726, 396	927, 755
From new scrap	92, 500 267, 300 65	212, 800 286, 900 69	198, 156 333, 890 61	313, 697 412, 699 76	500, 633 427, 122 86

<sup>&</sup>lt;sup>1</sup> Includes copper in chemicals as follows: 1939, 3,200 tons; 1940, 9,431 tons; 1941, 9,804 tons; 1942, 17,455 tons.

## CONSUMPTION

Available data on consumption of copper indicate that new high record rates of use were established in 1941 and again in 1942. The calculations were made upon the basis of copper available for use, or apparent consumption. Also, in estimating apparent consumption it has been assumed that copper used in the manufacture of primary

<sup>&</sup>lt;sup>1</sup> McBride, R. S., Insecticide Chemicals Needed For War Food Supply: Chem. and Met. Eng., vol. 50, No. 3, March 1943, pp. 101–103.

fabrications of copper is copper consumed. It is likely that statistics compiled upon a different basis (for example, by taking consumption as including only copper made into automobiles, electrical equipment, ships, etc.) would show very different results. Much copper leaves the country as primary fabrications and considerably more in manufactured products containing copper. Actual consumption data may be compiled at many points in the industrial process. The method of calculating the quantity of copper available for consumption is shown in the following table. It should be noted that exports and stocks include some refined secondary copper that cannot be determined separately and also that actual consumption of new copper would differ from the figures shown in the table by the changes in consumers' stocks.

New refined copper withdrawn from total year's supply on domestic account, 1938-42, in short tons

	1938	1939	1940	1941	1942
Total supply of new copperStock at beginning of year	794, 217 179, 000	1, 025, 779 181, 000	1, 381, 893 95, 500	1, 742, 303 91, 500	1, 809, 600 77, 500
Total available supply	973, 217	1, 206, 779	1, 477, 393	1, 833, 803	1, 887, 100
Copper exported <sup>1</sup> Stock at end of year	385, 223 181, 000	396, 406 95, 500	377, 108 91, 500	114, 753 77, 500	132, 467 84, 000
이렇게 이 크리고 있으로 보다	566, 223	491, 906	468, 608	192, 253	216, 467
Withdrawn on domestic account	406, 994	714, 873	1, 008, 785	1, 641, 550	1, 670, 633

<sup>1</sup> Includes refined copper in ingots, bars, rods, or other forms.

The usual discussion of consumption of copper by uses cannot be given owing to inability of the American Bureau of Metal Statistics, the source of previous data on this subject, to obtain and release information because of the war.

### STOCKS

The following table gives domestic stocks of copper as reported by primary smelting and refining plants. Stocks of blister and anode copper in transit from smelters to refineries are included under blister copper.

Stocks of copper at primary smelting and refining plants in the United States at end of year, 1938-42, in short tons

Year	Refined copper	Blister and materials in process of refining <sup>1</sup>	Year	Refined copper	Blister and materials in process of refining <sup>1</sup>
1938	181, 000 95, 500 91, 500	233, 000 260, 000 243, 000	1941 1942	77, 500 84, 000	240, 000 235, 500

<sup>&</sup>lt;sup>1</sup> Includes copper in transit from smelters in the United States to refineries therein.

COPPER 143

The second district the second second second

Total inventories of copper in the hands of smelters and primary refineries at the end of 1942 were virtually unchanged from those on hand at the beginning of the year, having gained less than 1 percent; refined stocks rose 8 percent and those of blister and unfinished materials at smelters, in transit to refineries, and at refineries fell 2 percent.

Figures compiled by the Copper Institute (published in the press before June) show that domestic stocks of refined, duty-free copper declined to 65,309 tons at the end of 1942 from 75,564 tons at the end of 1941 and 142,772 tons at the end of 1940. At the end of 1938 refined stocks were more than double those on hand at the end of 1940 and were more than four times those at the end of 1942. There are always differences between the stock data of the Bureau of Mines and those of the Copper Institute, due partly to a somewhat different coverage and partly to an arbitrary but permissible method used by the Copper Institute in designating the copper as domestic or foreign metal. This latter factor causes a time-lag difference between the

two sets of figures.

According to fabricators' statistics (also published in the press before June), there were large variations in their inventories in recent Stocks of refined metal, in-process material, and primary fabricated shapes totaled 339,376 tons at the end of 1940, declined to 295,813 tons at the end of 1941, and rose to 414,668 tons at the end Meanwhile unfilled purchases of refined copper in fabricators' hands fell from 326,269 tons at the end of 1940 to 241,335 tons at the end of 1941 and to 135,481 tons at the close of 1942. Fabricators' working stocks, which rise and fall according to plant activity, were 240,740, 291,515, and 340,547 tons, respectively. Unfilled sales by fabricators to customers rose from 414,892 to 547,468 to 613,005 Even the staggering figure of 613,005 tons at the end of 1942 marked a decline from the historic total of 689,177 tons at the end of June. Copper classed as "available for sale" was 10,013 tons at the end of 1940, and -304,675 and -403,403 tons, respectively, at the close of 1941 and 1942.

The quantity of copper delivered thus far to the Metals Reserve Co. aggregates the equivalent of more than a good year's production from domestic mines. Monthly allocations are made against these stocks, and at the end of 1942 only 15 percent of the total metal

delivered remained in the stock pile.

### PRICES

Reports to the Bureau of Mines from copper-selling agencies indicate that 1,086,000 tons of copper were delivered to domestic and foreign purchasers (excluding deliveries of foreign copper to the Metals Reserve Co.) in 1942 at an average price (f. o. b. refinery) of 11.8 cents a pound, unchanged from 1941 and 0.5 cent a pound higher than in 1940. The average price for 1942 is exclusive of bonuses paid for the overquota outputs of individual mines. Such bonuses are described later. Bonus payments added between 0.3 and 0.4 cent a pound to the average realization for copper in 1942, but only a relatively small proportion of total production benefited and that which did received 5 cents a pound above the ceiling price.

Average monthly quoted prices of electrolytic copper for domestic and export shipments, f. o. b. refineries, in the United States, 1941-42, in cents per pound

		1941			1942			
Month	Domestic f. o. b. refinery <sup>1</sup>	Domestic f. o. b. refinery 2	Export f. o. b. refinery <sup>2</sup>	Domestic f. o. b. refinery <sup>1</sup>	Domestic f. o. b. refinery 2	Export f. o. b. refinery ?		
January	11.87	11.819	10. 257 10. 414	11.87 11.87	11.775 11.775	11. 508 11. 700		
February March	11.87 11.87	11. 794 11. 814	10. 414	11.87	11. 775	11.700		
April	11.87	11.820	10.952	11.87	11.775	11.70		
May	11.87	11. 815 11. 810	10. 950 10. 950	11.87 11.87	11. 775 11. 775	11. 700 11. 700		
JuneJuly	11.87 11.87	11.812	10. 950	11.87	11.775	11.70		
August	11.87	11. 778	10. 950	11.87	11.775	11.70		
September	11.87	11. 775	11.027	11.87	11.775	11.70		
October	11.87	11. 775	11. 367	11.87	11. 775	11.70		
November	11.87	11. 775	11. 200	11.87	11.775	11. 70		
December	11.87	11.775	11. 200	11.87	11.775	11.70		
Average for year	11.87	11. 797	10. 901	11.87	11.775	11.68		

<sup>&</sup>lt;sup>1</sup> As reported by American Metal Market Co.
<sup>2</sup> As reported by Engineering and Mining Journal.

Average yearly quoted prices of electrolytic copper for domestic and export shipments; f. o. b. refineries, in the United States and for spot copper at London, 1933-42, in cents per pound

	1933	1934	1935	1936	1937	1938	1939	1940	1941	1942
Domestic f. o. b. re- finery 1	7. 15	8. 53	8. 76	9. 58	13. 27	10. 10	11.07	11.40	11.87	11.87
Domestic f. o. b. re- finery 2 Export f. o. b. refinery 2 London spot 2 3	7. 025 6. 713 6. 877	8. 428 7. 271 7. 496	8. 649 7. 538 7. 753	9. 474 9. 230 9. 465	13. 167 13. 018 13. 097	10.000 9.695 9.912	10. 965 10. 727 4 10. 066	11. 296 10. 770 (5)	11. 797 10. 901 ( <sup>5</sup> )	11. 775 11. 684 (5)

As reported by American Metal Market Co.
 As reported by Engineering and Mining Journal.
 Conversion of English quotations into American money based on average rates of exchange recorded by Federal Reserve Board of Treasury.
 Average for 8 months; thereafter, London Metal Exchange dealings suspended for duration of war.

Ceiling prices were placed on electrolytic and casting copper in 1941 and were described in the chapter of Minerals Yearbook, 1941, on this subject. In January 1942 the Metals Reserve Co. was authorized to buy copper produced at domestic mines, and fulfilling certain requirements, at 5 cents above the ceiling price, or at 17 cents a pound. Payments were to be made on production from February 1, 1942, and were to extend over 2½ years. The payments were to be made only on production over quotas set by the War Production Board and the Office of Price Administration. The plan was inaugurated to stimulate production from either new or high-cost properties, or both. When individual quotas were established the mines falling into preferred classes were found largely to have zero quotas, which entitled the total amounts produced to bonuses. Well-established, large properties were assigned such high quotas that they were entitled to virtually no benefits. It was necessary during the year to revise a number of quotas to eliminate inequities. Late in the year and early in 1943 it became desirable to revise downward many more to take care of the generally increased costs of production. In January 1943 the plan was extended to July 31, 1945. On May 1, 1943, it was an-

145 COPPER

THE REPORT OF THE PARTY OF THE

The state of the s

nounced that a special additional premium would be made available to small copper mines that produced less than 2,000 tons of copper in 1942 and required increased revenue to obtain maximum production. Individual cases were to be considered separately, and a special premium was to be paid at a rate to be fixed for each mine on production in excess of a special quota. Premiums and quotas were subject to adjustments at any time or revocation on 30 days' notice.

The premiums for less-than-carlots sold by producers and refiners were revised in January 1942, effective February 1. The ceiling prices l. c. l. on electrolytic, Lake, and other fire-refined copper and casting copper were set at 12% cents and 12 cents per pound f. o. b. shipping points, respectively. Premiums were no longer permitted on casting

copper sold by persons other than a producer or refiner.

Copper and copper-alloy scrap prices are discussed in the chapter

on Secondary Metals—Nonferrous.

The following official maximum prices, delivered to consumers' plants, have prevailed in the London market since December 18, 1939:

	£	Per long ton
Electrolytic, high conductivity	62	
Fire-refined: High conductivity	20	
High grade	62	70
Minimum, 99.7 percent	61	
Minimum, 99.2 percent	60	10
Hot-rolled black wire rods	65	10

# FOREIGN TRADE 3

Under ordinary circumstances, excess copper smelting and refining capacities in the United States are utilized to reduce crude materials from abroad which later are shipped from the country as refined copper or fabricated shapes. This business has been done mainly without the payment of the duty, or if the duty was paid and the copper was subsequently exported virtually all of the expenditure has been refunded. The conditions once considered normal, however, have disappeared. First of all, war demands have, temporarily at least, removed all excess capacity, and all the copper that can be obtained at home or abroad is urgently needed. Copper in refined form (primarily that from Chile), which used to go directly to Europe and which was temporarily stranded without adequate outlet after war was declared, was later welcomed in the United States. Every effort was made to supply adequate shipping tonnage to obtain every available pound of refined metal—an "about face" from the pre-war situation. As a consequence, imports of refined metal reached new heights in 1941 and again in 1942. Since the war started, receipts of copper have been largely from countries that furnished the principal amounts of crude copper before, but, as already stated, the accent has shifted to obtaining higher grades. One important defection is noted in the absence of the usual copper from Yugoslavia. There has been an even greater disruption of export movements. The large shipments to most European countries and to Japan, previously the

Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

principal destinations, have ceased. The United Kingdom is the one exception, as it now leads as a destination of copper from the United States and was one of the leading countries for many earlier years; the U. S. S. R. has taken large amounts, beginning in 1939. Copper is exported now only after careful scrutiny of the requests made and careful weighing of one need against another. Domestic requirements may go unfilled in favor of more urgent ones of our allies. Exports in 1941 and 1942 compared unfavorably with most other years in the twentieth century, and it was expedient that they did so. A noteworthy movement in 1942 was the shipment of over 32,000 tons of copper wire to the U. S. S. R., of nearly 13,000 tons to Egypt, and of nearly 8,000 tons to India. The export movement would be found to have been much larger than is evident from the records for refined and primary manufactures shown in this report, if data on the amounts of copper exported in such manufactured products as airplanes, tanks, and electrical apparatus were available separately.

### IMPORTS

As regards imports, the outstanding development of the past 2 years has been the increased receipt of refined copper to record-breaking proportions. This class of imports had little significance from the time the 4-cent tariff on copper went into effect in 1932 to the beginning of the present war. Refined copper began to reach the country in increasing quantities again in 1940, and imports were larger than ever before in 1941 and again in 1942. Since 1932 Chile has furnished virtually all of the refined copper entered, and it has come from mines controlled by nationals of the United States. Canada was an important contributor before that time. In both 1941 and 1942 Chile supplied 99 percent of the total refined copper imported. the absence of sufficient shipping accommodations to bring all desired commodities into the country, there were declines in the receipts of some of the lower grades of copper in 1942 as compared with 1941 and 1940, although most grades compared favorably with other recent years before World War II. Receipts of copper classed by the Department of Commerce as "unrefined black blister and converter copper in pigs or converter bars" were mainly from Chile, Mexico, Belgian Congo, Peru, Canada, and British Africa in 1941 and 1942. Chile supplied less of this grade of copper in 1941 than in 1940 and fell again in 1942. Peru followed the same pattern, and Canada sent only about a fourth as much in 1942 as in either 1941 or 1940. gained in 1941 and again in 1942, and Belgian Congo, whereas furnishing less in 1942 than in 1941, supplied considerably more in both years than in 1940. Belgian Congo also sent generous amounts of regulus or black copper, being the outstanding supplier of this grade. Imports from Belgian Congo in 1941 and 1942 were largely earmarked for reshipment to the United Kingdom after refining. Imports of the lower-grade classes of concentrates and ores came mainly from Canada, Cuba, Chile, and other Western Hemisphere sources in 1942, and Western Hemisphere sources predominated likewise in 1941. ada was well ahead of all others in shipping copper concentrates; receipt from this source and from Mexico make no strain on ocean shipping facilities. A noteworthy quantity of copper in concentrates was shipped from the Philippine Islands in 1941. Unfortunately, the resources of these islands added to Japan's supplies in 1942.

Copper (unmanufactured) imported into the United States, 1941 and 1942, by countries, in short tons 1

Country	Ore (copper content)	Concentrates (copper content)	Regulus, black or coarse copper, and cement copper (copper content)	Unrefined black blis- ter and converter copper in pigs or con- verter bars	Refined in ingots, plates, or bars	Old and scrap copper, fit only for remanufac- ture, and scale and clippings
1941						
Africa, British:		4000				
Union of South		193	59			21
Other South		653		6, 929		
Argentina	2	41	116			
Australia	1, 150		45 505			
Belgian Congo		38	45, 505	36, 451		
Bolivia	191	6, 265	1, 816			
Burma Canada	117	34, 533	413	22, 420	3, 912	1, 887
Chile	1, 199	1,612	2	114, 430	343, 082	1, 867
Colombia	1, 155	1, 012	0 1 4 4 4 4 T	111, 100	020,002	17
Cuba	124	7, 943				1
Curação (NWI)						54
Ecuador	162	3, 375				
Honduras		136				
Mexico Newfoundland and Lab-	1, 150	7, 122		46, 136		51
Newfoundland and Lab-		COMMERCIAL PROPERTY.	COUNTY OF THE PROPERTY OF THE PARTY OF THE P	Berlin Leathard and Standard Standards		
rador Panama, Republic of	5	5, 811				.5
Panama, Republic of						62 33
Peru	(2)	4,821	42	30, 840		30
Philippine Islands	3	<sup>2</sup> 3, 964 17	4			111
Other countries	0	11	- 4			111
	4, 562	76, 539	47, 958	257, 206	346, 994	2, 286
1942						
Africa, British:						
Union of South		16	4, 252	14, 567		
		321	24	4, 224		
Argentina	2	55				
Australia	3, 391	40		161		
Belgian Congo	J	(3)	62, 542	29, 068		
Bolivia	304	5, 120				
Burma		355	1, 249			
Canada	14	27, 481 6, 691	(3) 306	5, 822 92, 246	820 391, 785	090
Chile	504	0,091	(9)	94, 240	991, 789	
ColombiaCuba		8, 867			(3)	
		0,001			(-)	
Ecuador		1,482	270		500	
Honduras		(3)	0			
Mexico	735	4, 986		51, 846		
Newfoundland and Lab-	•••					
rador		4, 120				
Panama, Republic of						
Perm	516	5, 501	357	22, 300	1, 934	
Philippine Islands	(2)	2 256				
Other countries	14	4	(3)	1, 838		490
	5, 480	65, 303	69,000	222, 072	395, 039	1,080

# Copper (unmanufactured) imported 1 into the United States, 1938-42

Year	Short tons	Year	Short tons
1938	252, 164 336, 297 491, 342	1941 1942	735, 545 757, 974

<sup>1</sup> Data include copper imported for immediate consumption plus material entering country under bond.

<sup>&</sup>lt;sup>1</sup> Data include copper imported for immediate consumption plus material entering the country under bond.
<sup>2</sup> Some copper in "ore" and "other" from the Philippine Islands is not separately classified and is included under "concentrates."
<sup>3</sup> Less than 1 ton.

### **EXPORTS**

Total exports of copper in 1942, including those of the primary steps of manufacture, were over a third larger than the extremely low total for 1941. Of our principal pre-war customers—Japan, Germany, the United Kingdom, Italy, France, Belgium, and Sweden-only the United Kingdom remains. Three of these countries are our enemies in the present conflict, two are under enemy domination, and the sixth is an uneasy neutral surrounded by shipping and other complications. It is a sad commentary that Japan received nearly 22,000 tons of copper from the United States in 1941. The United Kingdom sharply increased its orders for copper in 1942 and took more of the refined class—the principal one—than it has since 1918. The U.S. S. R., a negligible buyer before the war, received the second-largest quantity of copper shipped from the United States in 1942. recent sharp gains in shipments of insulated and other copper wire and cable to U.S. S. R., Egypt, and India (British) are worthy of note. In 1942 over 32,000 tons were shipped to the U.S.S.R., nearly 13,000 to Egypt, and nearly 8,000 to India.

The following table gives the destinations of exports of copper and primary manufactures in 1941 and 1942. The chapter on Copper from Minerals Yearbook, 1941, contains a table showing exports by countries for 1937 to 1940 and indicating the revolution in flow of copper from the United States since the outbreak of war in Europe.

# Copper exported from the United States, 1941-42, by countries, in short tons

	Ore, concen- trates, com-	Refl	ned						
Country	position metal, and unrefined copper (cop- per content)	Bars, ingots, or other forms	Rods	Old and scrap	Pipes and tubes	Plates and sheets	Wire (except insulated)	Insulated wire and cable	Other copper manufactures
Argentina Australia Brazil Brazil Burma Canada Chile China Colombia Cuba Egypt Hong Kong India, British Japan Kwantung Mexico Netherlands Panama, Republic of Philippine Islands U. S. S. R United Kingdom Other countries	3 (1)	892 3, 364 6, 718 2, 000 284 15 6, 461 45 1 1, 566 14 2, 437 16, 934 2, 437 16, 934 3, 043 978 88 176 5, 768 53, 734	7 483 314 3 326 (1) 3 6 1 6,889 1,680 1,344 4 37 4 4 9	26 112 	93 280 1578 39 70 31 123 4 2 166	17 228 125 679 19 108 117 31 3 10 1,160	313 51 218 362 175 548 1, 197 175 135 371 6 817 	1, 559 806 297 472 1, 268 628 374 710 995 3, 363 288 368 1 145 824 2, 783 1, 308 2, 773 1, 786 4, 105	(2)
Total value	12 \$3,874	103, 602 \$23, 351, 231	11, 151 \$2, 934, 584	3, 258 \$722, 943	2, 132 \$1, 173, 882	3, 782 \$1, 574, 750	7, 392 \$2, 533, 373	27, 576 \$13, 901, 638	(2) \$1, 493, 265

See footnotes at end of table.

# Copper exported from the United States, 1941-42, by countries, in short tons—Continued

	Ore, concen- trates, com-	Refi	ned						
Country	position metal, and unrefined copper (cop- per content)	Bars, ingots, or other forms	Rods	Old and scrap	Pipes and tubes	Plates and sheets	Wire (except insulated)	Insulated wire and cable	Other copper manufactures
1942 Argentina Australia Brazil Burma	(1)	(¹) 1,131	(1) 2 (1) 2		43 2 20 (1)	81 50 19	30 128 63 225	396 1, 267 284 45	
Canada Chile China Colombia Cuba Egypt Hong Kong	2	(1)	(1) (1) (1)	1	650 7 (1) 7 74 1	143 6 6 1 17	32 354 342 33 63 4,015	991 437 117 145 335 8,826	
India, British Japan		251	1		9	170	2, 544	<sup>(1)</sup> 5, 278	(2)
Kwantung Mexico Netherlands Panama, Republic of Philbrid Schools	(1)	3,376	6		85	20	200	1, 157	
Paning, Republic of Philippine Islands U. S. S. R.		15, 238	172		3,629	(1)	(¹) 415	37	
United KingdomOther countries	3, 422	108, 683 161	34 11	1, 130 1, 103	3, 629 30 220	1,078 131 188	169 1,877	31, 898 2, 140 7, 077	
Total value	3, 424 \$796, 062	132, 141 \$29, 754, 554	\$134, 686	2, 234 \$472, 607	4, 778 \$5, 757, 806	1, 910 \$905, 658	10, 490 \$3, 773, 341	60, 430 \$37, 210, 491	\$3, 75 9, 403

<sup>1</sup> Less than 1 ton.

Figures for quantity not recorded.

# Copper 1 exported from the United States, 1938-42

	Shor	t tons	Total		Shor	Total	
Year	Metallic <sup>2</sup>	Total	value	Year	Metallic <sup>2</sup>	Total	value
1938 1939 1940	421, 012 427, 517 427, 650	422, 014 427, 579 427, 944	\$86, 119, 848 96, 321, 365 108, 534, 217	1941 1942	158, 893 212, 309	158, 905 215, 733	\$46, 196, 275 78, 805, 205

<sup>&</sup>lt;sup>1</sup> Exclusive of "other copper manufactures" valued at \$689,008 in 1938; \$863,561 in 1939; \$1,584,441 in 1940: \$1,493,265 in 1941; and \$3,759,403 in 1942. 

<sup>2</sup> Exclusive of ore, concentrates, and composition metal; exclusive also of unrefined copper, figures for which are not separable from those for ore and concentrates.

# Brass and bronze exported from the United States, 1941-42, by classes

	19	41	1942		
Class	Short tons	Value	Short tons	Value	
Ingots Scrap and old Bars and rods. Plates and sheets. Pipes and tubes Pipe fittings and valves Pipe fittings and valves Plumbers' brass goods. Wire of brass or bronze. Brass wood screws. Hinges and butts of brass or bronze. Other hardware of brass or bronze. Other brass and bronze manufactures	124 722 8, 603 30, 770 1, 540 1, 527 655 3, 769 (1) (1) (1)	\$41, 739 115, 991 3, 139, 014 11, 377, 789 2, 101, 318 792, 695 1, 897, 069 149, 650 135, 778 547, 753 5, 304, 237	268 168 10, 689 63, 172 2, 752 1, 694 230 3, 517 (1) (1) (1)	\$85, 342 28, 333 3, 719, 266 24, 056, 349 1, 784, 002 1, 862, 328 360, 756 64, 610 56, 956 341, 215 6, 093, 210	

<sup>1</sup> Weight not recorded.

# Unmanufactured brass exported from the United States, 1938-42 [Ingots, bars and rods, and plates and sheets]

Year	Short tons	Value	Year	Short tons	Value
1938	1,823	\$677,809	1941	39, 497	\$14, 558, 425
1939 1940	6, 476 90, 907	1,946,578 30,801,796	1942	74, 129	27, 860, 957

# Copper sulfate (blue vitriol) exported from the United States, 1938-42

Year	Short tons	Value	Year	Short tons	Value
1938 1939 1940	15, 625 14, 620 27, 740	\$1, 229, 317 1, 157, 498 2, 293, 983	1941 1942	34, 511 - 35, 280	\$2,950,714 3,443,922

# WORLD ASPECTS OF COPPER INDUSTRY

Figures on production of copper—and for that matter on all other materials—have not been available for many countries since or immediately before the outbreak of World War II. Copper is one commodity of which the United Nations retain a preponderant share of the world total, however, and upon the basis of available information it is safe to assume that more copper was produced in the world in

1942 than in any previous year. The world's largest sources—the United States, Chile, Canada, Northern Rhodesia, and Belgian Congo-were producing at record or near-record levels, and copper from these countries (and from others as well) was all directed toward filling United Nations needs. Nevertheless, the United Nations had insufficient supplies to take care of their expanded war demands for military and essential civilian requirements. Certainly the Axis Powers, much less favored with reference to copper, at least, were hard-pressed to make ends meet. The overrunning of neighboring countries in Europe by the Germans and Italians added principally Yugoslav copper as new supplies. Much copper was also gained by seizing inventories of metal in the conquered territory and from intensive scrap drives therein. The yield in copper and copper products from conquered nations other than Yugoslavia is not of a nature to continue, however, and the situation as regards copper, therefore, must be rapidly worsening. Likewise Japan, despite great gains in raw material supplies, did not succeed in acquiring areas that can yield appreciable quantities of copper. The production of the Philippine Islands was the principal and doubtless only gain in this regard, and under 10,000 tons of copper probably will be obtained annually from that source. Unlike Germany, Japan did not conquer territory that would yield noteworthy quantities of copper, copper alloy, and scrap stocks.

# World mine and smelter production of copper, 1939-42, in metric tons

[Compiled by B. B. Waldbauer]

Country		Mi	ne			Sme	lter	
Country	1939	1940	1941	1942	1939	1940	1941	1942
North America: Canada Cuba.	276, 157 9, 964	297, 371 9, 559	291, 802 9, 838	274, 594 (²)	1 229, 367	1 256, 294	(3)	(2)
Mexico. Newfoundland United States.	44, 390 10, 341 660, 717	37, 602 9, 426 796, 582	48, 716 6, 651 869, 214	51, 379 5, 666 979, 811	39, 045 8 698, 323	31, 252 8 922, 364	40, 914 8 1, 015, 346	(2) 8 1, 111, 458
	1, 001, 569	1, 150, 540	1, 226, 221	(2)	966, 735	1, 209, 910	(2)	(2)
South America: Bolivia. Brazil Chile	4 4, 056 14 339, 173	4 6, 660 (2) 352, 010	4 7, 274 (2) 465, 467	4 6, 376 (2) (2) (2)	324, 591	336, 861	453, 594	477, 783
EcuadorPeru	35, 616	1, 133 43, 965	2, 894 36, 822	<sup>(2)</sup> 37, 000	34, 115	33, 678	28, 289	<sup>(2)</sup> 29, 473
	378, 861	(3)	(2)	(2)	358, 706	370, 539	481, 883	507, 206
Europe: BelgiumBulgaria	320	560	(2)	(2)	<sup>8</sup> 65, 850	(2)	(2)	(2)
Cyprus. Finland France. Germany 6 8 Austria 6 8	24, 384 11, 797 (7) 30, 000	(2) 6 20, 000 (2) 35, 800	(2) 6 18, 000 (2) (2)	(2) (2) (2) (2)	13, 246 (7) 9 66, 000	(2) (2) (2)	6 18, 000 (2) (2)	(2) (2) (2)
Hungary. Italy. Norway. Portugal.	(7) (7) 20, 358	(2) (2) 8 20, 000 (2)	(2) (2) (2)	(2) (2) (2) (2)	(7) • 10, 515	(2) 6 7, 250	(2) (2)	(2) (2)
Fortugal. Rumania. Spain. Sweden. U. S. S. R. <sup>10</sup> United Kingdom Yugoslavia.	(7) (7) 9, 610 11 144, 000 (7) 64, 200	(2) (2) (2) (2) 11 157, 000 (3) (2)	(9) (2) (3) (9) (9) (9) (9)	(2) (2) (2) (2) (2) (2)	(7) 10, 445 11, 076 144, 000 6 4, 000 41, 658	(2) 9, 422 6 12, 500 157, 600 6 4, 500 8 42, 951	(2) (2) (2) (2) (2) (2)	(2) • [7, 070 • 12, 000 (2) (2) (2) (2)
	(7)	(2)	(2)	(2)	(7)	(2)	(2)	(2)

See footnotes at end of table.

# World mine and smelter production of copper, 1939-42, in metric tons-Continued [Compiled by B. B. Waldbauer]

Country		Mine Smelter							
Country	1939	1940	1941	1942	1939	1940	1941	1942	
Asia: Burma	6 3, 365	(2)	(2)	(2)					
Undia, British	(7)	(3) (13) (2)	(²)	(2) (2)	6, 640	<sup>(13)</sup> 8 6, 900	<sup>14</sup> 163 (²)	(2) (2)	
Japan Proper Taiwan Netherlands Indies		6 11 125,000 6 4,000 (2)	(2) (2)	(2) (2)	6 104, 000	<sup>6</sup> 125, 000	(2)	(3)	
Netherlands Indies Philippine Islands Turkey U. S. S. R	7, 496 11 5, 917 (10)	9, 259 11 8, 731 (10)	6 9, 900 11 10, 500 (10)	(2) (2) (2) (10)	5, 917 (10)	8, 731 (10)	10, 500 (10)	(2) (10)	
	(7)	(2)	(2)	(2)	<sup>10</sup> 116, 558	(2)	(2)	(2)	
frica: Algeria Algeria Belgian Congo Rhodesia: Northern Southern	11 ì22, 649	(2) 11 148, 619 (2) (2)	(2) 6 11 165, 000 245, 622	(2) 6 11 168, 000 254, 654	122, 649 215, 065	148, 619 6 231, 330	6 165, 000 (2)	6 168, 000 (2)	
South-West Africa Union of South Africa	3 530	1, 485 13, 350	(2) (2) (2)	(2) (2)	14, 089	17, 024	15 16, 038	15 19, 747	
ceania: Australia	(7)	(2) (2)	(2) (2)	(2) (2)	351, 803 20, 219	(²) 22, 680	(2) (2)	(2) 6 23, 000	
	2, 251, 000	(2)	(2)	(2)	6 2, 182, 000	(2)	(2)	(2)	

<sup>1</sup> Copper content of blister produced.

<sup>1</sup> Copper content of blister produced.
2 Data not available.
3 Smelter output from domestic and foreign ores, exclusive of scrap. Production from domestic ores only, exclusive of scrap, was as follows: 1939, 646,524 tons; 1940, 824,703 tons; 1941,
4 Copper content of exports.
5 Figures represent blister copper only. In addition to blister copper, Belgium reports a large output of refined copper which is not included above as it is believed produced principally from crude copper from Belgian Congo and would therefore duplicate output reported under the latter country.
5 Estimate included in total.
5 According to Yearbook of American Bureau of Metal Statistics.
6 Exclusive of material from scrap.
10 Output from U. S. S. R. in Asia included under U. S. S. R. in Europe.
11 Exports of ingots and slabs.
12 Exports of ingots and slabs.
13 Less than 1 ton.
14 January to August, inclusive.

<sup>14</sup> January to August, inclusive.
18 January to October, inclusive.

THE REPORT OF THE PARTY OF THE

## REVIEW BY COUNTRIES

Australia.—The efforts to augment production in Australia were extended in 1942. Figures showing results of these efforts are not available for the mines. As labor shortages were prevalent and difficulties were experienced in obtaining needed supplies and equip ment, it may well follow that production did not gain as expected in 1942. The Government granted a further advance in price from £A86 10s. to £A105 a ton. The basic price to producers for their normal output was to be £A100, with a bonus of £A5 for each ton in excess.

In November it was reported that large-scale mining of copper ore had begun at the Mount Isa mine, Queensland. The stripping of overburden at the Mount Morgan mine was reaching a stage that should permit mining of a greater tonnage of ore. Here open-cut operations to the 700-foot level were in prospect. Ore from the Mount Chalmers mine is to be transported to Mount Morgan for reduction when production begins. In the year ended September 30, 1942, a larger tonnage of ore was treated at the Mount Lyell mine, Tasmania, than in the previous year, but the average grade was lower and only a small increase in the output of copper resulted. Ore reserves at Mount Lyell were given as 14,850,000 tons of ore, averaging 1.14 percent copper, 0.07 ounce silver, and 0.012 ounce gold. Preliminary surface inspection, for the Government, of South Australia mines, idle for many years, and examination of previous records for the district led to the conclusion that absence of sufficient ore in any one section to permit working from one shaft prevented the revival The report stated that unless geophysical surveying, in conjunction with diamond drilling, can locate new ore bodies worth developing, it is not feasible to work the ore remaining in the mines at Moonta and Kadina. A diamond-drilling program was suggested.

Belgian Congo.—Following a visit of several months in Belgian Congo, the Belgian Minister of Colonies stated that the colony was producing at the rate of about 160,000 tons of copper annually and could add 30,000 tons if new equipment were available. Late in 1942 a reliable authority estimated that 168,000 metric tons would be produced in 1942. The estimated production capacity is reported as 200,000 tons. In the first part of 1943 an extreme drought lasting several months threatened a 20,000-ton drop in the production rate, with a more serious drop in prospect if enough coal could not be obtained from Northern Rhodesia for the steam power plant. prepared by the Belgian Information Office stated that under purchase agreements with the United Kingdom a minimum of 124,000 English (126,000 metric) tons was to be purchased in 1941 and a minimum of 144,000 long (146,000 metric) tons in 1942. 144,000 long (146,000 metric) tons in 1942. These figures were contrasted with the 3,766 long (3,826 metric) tons imported into the These figures were con-United Kingdom from Belgian Congo in 1914 and 13,178 long (13,390 metric) in 1916. Large amounts of Belgian Congo copper began to come to the United States again in 1940 following a lull of a number of years. In 1941 the United States received 41,300 metric tons of regulus, black or coarse copper, and cement copper and 33,100 tons of unrefined black blister and converter from Belgian Congo, compared with 56,700 tons and 26,400 tons, respectively, in 1942.

Bolivia.—Early in 1942 a contract was entered into with the Metals Reserve Co. for the sale of all copper produced to that organization, on the same basis as the one covering Chilean copper and other items. Exports in 1942 aggregated 6,376 metric tons compared with 7,274 tons in 1941.

Canada.—Contrary to expectations and to forecasts in the press, the production of copper in Canada did not establish new peak records in 1941 and 1942. Figures for 1940 recently made available indicate that the peak rate was established in that year, with a mine total of 327,797 short tons; the total for 1941 was 321,658 short tons, and for 1942, 302,690 tons. There is little doubt that successive record outputs would have been made as expected if it had not been for labor difficulties, such as those in the United States.

The Bureau of Mines, Ottawa, summarized the copper operations in Canada recently. That organization stated that Canada's output of copper is obtained from the copper-nickel ores of Sudbury, Ontario; the copper-gold, copper-zinc, and copper-pyrites ores of western Quebec; the copper-zinc ores of northern Manitoba; and the copper

ores of British Columbia.

The Britannia Mining & Smelting Co. operated its mine and concentrator at Britannia Beach, British Columbia, shipping the copper concentrate as previously to Tacoma, Wash. A reduction of approximately 50 percent in operations in 1942 was due to labor shortage. The production of Granby Consolidated Mining, Smelting & Power Co. approximated 86 percent of that in 1941. Ore reserves once more gained during the year. Anyox Metals, Ltd., is conducting a diamond-drilling campaign at the Hidden Creek and adjoining properties near Anyox.

Preparations were under way for operation of the Tyee zinc-lead-copper property near Chemainus, Vancouver Island, by Twin "J" Mines, Ltd., under supervision of Wartime Metals Corporation, Canadian counterpart of the Metals Reserve Co. of the United States.

Production is expected early in the summer of 1943.

At Flin Flon, Manitoba, Hudson Bay Mining & Smelting Co., Ltd., operated its mine, concentrator, smelter, and zinc plant at increased capacity. A fifth copper roaster was installed and put in operation, and the reverberatory furnace was enlarged. This company is said to have proved an important copper-zinc ore body at Schist Lake by exploratory work. A subsidiary company is equipping the old Mandy mine with a 200-ton concentrating plant, ending many years of idleness at this property, and production is expected in the first half of 1943. Sherritt Gordon Mines, Ltd., has indicated a large tonnage of low-grade copper ore by diamond drilling in a section of its property north of the main ore body. The company mine and mill were operated at capacity.

The leading producer in Ontario, as usual, was the International Nickel Co. of Canada, Ltd., which operated its Frood, Frood Open Pit, Creighton, Levack, and Garson mines and started sinking operations at the Murray and Stobie mines. The concentrator at Copper Cliff was operated at capacity, and the capacity was increased to treat additional tonnages of ore from the Open Pit mining operations. Falconbridge Nickel Mines, Ltd., operated its mine and smelter at

<sup>4</sup> Canada Bureau of Mines, Canadian Copper Operations in 1942 Reviewed: Quoted in the Northern Miner, vol. 29, No. 7, May 6, 1943, p. 20.

COPPER 157

いっこう こうていていている 大きないない ないかんしょう かんしょうしょうしょう

capacity. The capacity of the smelting plant was increased. Kam-Kotia Porcupine Mines, Ltd., a project of Wartime Metals Corporation, is opening the Jamieson copper property in Robb Township, 20 miles northeast of Timmins.

Metals Controller Geo. C. Bateman of Canada stated that the United States was aiding mining in Canada, that 17 properties were being operated, and that production plans called for the recovery of

46.000 tons of copper.

Chile.—In an effort to supply a substantial part of the needs of the United States Government for copper to feed its war machine, Chile again pushed its copper-production rate into new high territory. put totaled 477,733 metric tons compared with the previous record tonnage of 453,594 tons in 1941, and the country safely maintained its place as the second most important producer in the world. Metals Reserve Co. contracted to purchase all of Chile's output. Despite efforts of various United States Government agencies to give all possible help toward increasing the output from Chilean mines, impediments to satisfactory operation were numerous. These involved inadequate supplies of machinery and fuel and scarcity of competent technical personnel. It probably affected small operations more seriously than large ones. The predominant copper-producing mines at Chuquicamata, Potrerillos, and Sewell maintained a high level of activity throughout the year. The Chile Exploration Co. produced 47.25 percent of the country's total, Andes 19.17 percent, and Braden 30.76 percent. Smaller producing mines in Central Chile (according to the Annual Review number of the Engineering and Mining Journal, February 1943) included the Tocopilla, with mills at Tocopilla (300 tons) and Ovalle (700 tons); Ojancos, at Copiapó; and Farellon Sanchez, Merceditas, Volcan, and Carlota, in the Maipo Valley near Santiago. The Chagres and Naltagua smelters operated at capacity; the former handled concentrates produced in the El Cobre and Caracoles mills and the latter received the production of the 500ton Disputada mill. The Punitaqui mine near Ovalle treated auriferous copper ore in a 400-ton selective flotation plant. A new company was formed to exploit the Cerro Negro mine, 40 km. from Cabildo, Province of Aconcagua; the Compagnie Minière du M'Zaita is ready to exploit the Cerrado mine; and the Carrizal Consolidated has combined the mining claims of Carrizal under one controlling interest. The Caja de Credito Minero was expected to blow in a matte furnace at Carrizal in March.

At the request of the United States Government the Chile Exploration Co. is expanding and enlarging the mining and treatment facilities for copper production at Chuquicamata to increase its joutput substantially. The project involves the expenditure of about \$5,000,000, to be advanced by the Defense Plant Corporation; the advance is to be retired as the copper produced from the additional

facilities is sold.

Of the copper exported, the United States received by far the largest amounts. Copper exported as electrolytic copper totaled 264,481 metric tons, of which the United States was the destination of 238,762 tons, Brazil 15,197, and Argentina 10,221. Standard copper exports were 233,763 tons, of which 229,401 were for the United States and 3,732 for Uruguay. The United States was scheduled to receive all of the 14,176 tons of concentrates and the 1,969 tons of ore shipped from the country.

Ecuador.—According to the Annual Report of Commerce and Industries for 1942, toward the latter part of the year copper was being exported from the country in the form of blister copper instead of as concentrates. Exports for the year were given as 417 metric tons of

copper in bars and 7,407 tons of copper concentrates.

Finland.—The Metal Bulletin (London) of July 17, 1942, stated that the Outokumpu Copper Co., overwhelmingly the principal producer in the country, produced 18,000 metric tons of copper in 1941 and that Finland suffered a severe shortage in this metal despite the fact that normal consumption is only 7,000 tons annually. The shortage resulted from the retention of only 3,000 to 4,000 tons of the total for home consumption. Obviously, with domestic consumption needs unfilled, there must have been urgent reasons for shipment of such a large portion of the total out of the country. Germany is believed to have been the destination of the shipments.

Germany.—Speculation increases as to how Germany's inaccessibility to adequate copper supplies is being overcome as war progresses, and the time factor—from a copper viewpoint at the very least—moves to Hitler's disadvantage. Copper is one of the commodities of which the United Nations control by far the preponderant share, and even the United Nations promptly felt a pinch in regard to its supplies. The Metal Bulletin (London) of December 15, 1942, makes the following suggestions as to how Germany's problem has been

managed thus far.

(a) She started off with large supplies of manufactured copper and brass components accumulated while the rest of the world was still blissfully anticipating peace, (b) she also held considerable stocks of raw copper at the outbreak of war previously sold to her by her future enemies, (c) she captured appreciable stocks of virgin copper when she successfully overran various neighboring countries, (d) she has stripped most of Europe of all kinds of copper articles, (e) she has to some extent offset her lack of copper by substituting aluminum, zinc, plastics, etc.

The partial solution under "(d)" is surely not an entirely satisfactory one. Increasing amounts of scrap materials are used ordinarily by both participants in the progress of a war. With Germany, however, the proportion of scrap used must necessarily be larger than in the United Nations. The increased consumption of scrap materials containing a wide variety of metals in widely varying proportions presents metallurgical problems that tend to reduce maximum efficiency and capacity output. No new statistical data can be added to those

presented in earlier Minerals Yearbook chapters on Copper.

Mexico.—Mine output of copper in Mexico has gained in the past 2 years; 51,379 metric tons were produced in 1942 and 48,716 in 1941. Both years were above the records for previous years since 1931, though much below the annual average of 61,700 tons for 1923–31. No doubt the improved rate in 1942 is due in part to agreements between Mexico and the United States, signed in April, whereby the Metals Reserve Co. was to purchase, for the period of the agreement, copper and other metals at prices that were expected to stimulate increased production. Under this agreement the Mexican Government assures the mining industry of a stabilized tax policy, no increases in railroad rates on mineral products, and cooperation in other ways to facilitate increased production. The Mexican Government and the Mexican Mining Labor organizations also gave assurances of a cooperative and liberal attitude in applying labor laws and regulations applying to certain phases of mining operations.

159

At the request of the United States Government, The Cananea Consolidated Copper Co., South America, a subsidiary of Greene Cananea Copper Co., is developing an extensive body of low-grade copper ore adjacent to its present mine and plant at Cananea, Sonora. The company is constructing treatment facilities, involving an expenditure of approximately \$12,000,000, designed to increase the production of copper substantially. The construction will be financed through the Metals Reserve Co.

The Moctezuma Copper Co. has entered a contract with the Metals Reserve Co. under which the Pilares mine is to be unwatered to the 2,100 level so that the lower levels can be reconditioned and production increased. Under the contract, Metals Reserve is paying the cost of that work, the cost of operating all the properties of the Moctezuma Copper Co., and a small operating profit and receives the copper

 ${f produced}.$ 

Early in 1943 operations of the Boleo Copper Co. in Lower California were facing possible curtailment owing to difficulties in pro-

curing operating supplies.

Northern Rhodesia.—The supposition that Northern Rhodesia was continuing to break production records, mentioned in Minerals Yearbook, 1941, was not borne out by confidential data made available early in 1943. These showed that the production of 245,622 metric (241,744 long) tons for 1941 was down somewhat from the record of 254,904 metric (250,879 long) tons in 1938 and that the output of 254,654 metric (250,634 long) tons in 1942 just about equaled that for 1938. The details, by mines, for 1941 and 1942 were as follows:

					1941	1942
	1986				(Long	84. 512
Mufulira		 	 		37, 791	
Nchanga		 	 		l <b>5, 804</b>	13, 523
Nkana	14.7 (4.5)		 	(	36, 741	82, 801
Roan Antelope		 		7	71, 408	69, 798
TOTH Amerobe		 	 			

In a report covering mineral resources of this area, the Mineral Resources Department of the Imperial Institute,<sup>5</sup> London, gives the following information on copper:

The Copperbelt of Northern Rhodesia is an area some 50 miles long and 25 miles wide along the upper reaches of the Kafue river, close to the Katanga border of the Belgian Congo. Several copper deposits are known outside this area, \* \* \* but they are insignificant in size when compared with those of the Copperbelt and none of them is now worked. Natives and Arabs had worked copper at Luanshya and Bwana Mkubwa before the arrival of Europeans whose attentions were therefore soon attracted to these deposits. Development work commenced at Bwana Mkubwa in 1903 and ten years later copper concentrates were exported from the mine. The ores, however, were of relatively low grade compared with those mined profitably in the Katanga, and being oxidized proved difficult to treat, so that when thick deposits of clean sulfide ores averaging 4 per cent of copper were found at Luanshya in 1925 interest in the oxidized ores dwindled. The Luanshya discovery led to the opening up of the Roan Antelope mine, and intense prospecting and geological work followed by drilling soon proved the existence of several enormous sulfide ore bodies in other parts of the Copperbelt. Despite the set-back caused by the world economic depression, copper smelting began at Roan Antelope in 1931, at Nkana in 1932, and at Mufulira in 1937

The ore deposits occur in synclinal areas in the lower beds of the Mine Series and are generally considered to be of epigenetic origin and related to the intrusion of the Younger Granites, although a syngenetic theory of origin has also been advanced. The ores consist of altered shales and felspathic sandstones containing finely disseminated sulfides, principally chalcocite, bornite, and chalcopyrite.

Imperial Institute Bulletin, vol. 40, No. 4, October-December 1942, pp. 298-301.

Most of the deposits consist entirely of sulfides, but the Nchanga ore body contains mixed sulphide and oxidized ores and the Nchanga Extension is largely oxidized ore, malachite being the principal mineral. The ore bodies are sharply defined, gradation into the country rock being exceptional. In form the deposits are beds, usually steeply inclined, and frequently 25 or 30 feet in thickness, but in the Mufulira mine three beds up to 60 feet in thickness occur, and in places two coalesce to form a bed 100 feet thick. The proved reserves of the larger deposits in June 1939, were as follows, taken in order from south to north.

Roan Antelope	Reserves (long tons) - 98, 595, 000	Percent of copper
Baluba	- 98, 995, 000 - 19, 000, 000	3. 43 3. 47
Nkana and Mindola Chambishi	- 101, 792, 000	3. 43
Mufulira	- 22, 000, 000 - 96, 800, 000	3. 46 4. 39
Nchanga	_ 128, 375, 000	1 4, 66

1 2.53 percent present in oxide minerals and 2.13 present in sulfide minerals.

Further reserves exist which have not yet been proved, and according to the Commissioner of Mines it is probably safe to say that there are at least 750 million tons of high-grade copper ore in the Territory. The proved reserves are greater than those of any other country and the ores are richer than those of the major copper producers, but the annual output of copper is still exceeded by that of the United States, Chile, and Canada.

The producing mines are evenly spaced through the Copperbelt, the Roan Antelope mine at Luanshya in the south, the Nkana mine 21 miles to the northwest, the Mufulira mine 20 miles north of Nkana, and Nchanga, where a pilot mill commenced production in 1939, 29 miles northwest of Nkana. Shafts have also been sunk at the Chambishi mine between Nkana and Nchanga. The Bwana Mkubwa deposit at the southeast corner of the Copperbelt was found to have relatively small ore reserves. A special ammonia leaching process was necessary to treat the ore but, although more than 20,000 tons of copper were thus produced between 1926 and 1930, the process was abandoned and the plant has been dismantled. Each mine has its own smelter producing extremely pure blister copper, and at Nkana there is an electrolytic refinery. From the start of smelting in 1931 until the outbreak of the present war, however, copper production was restricted for economic reasons by agreements with other major copper producers of the world. Between 1936 and 1939 the copper production of the different mines was as follows:

	1936	1937	1938	1939
Nkana, electrolytic copper Nkana, blister copper Roan Antelope, blister copper Mufulira, blister copper Nchanga, blister copper	28, 012 28, 092 56, 448 29, 782	30, 740 54, 475 78, 349 44, 614	31, 367 49, 514 71, 930 60, 220	29, 654 50, 126 68, 904 61, 669 1, 315
Total	142, 334	208, 178	213, 031	211, 668

<sup>&</sup>lt;sup>1</sup> Smelted at Nkana.

The quantities of ore treated during 1939 and the copper produced, together with their copper contents, are shown in the following table.

	Omo tra	. boton	Copper recovered			
Mine	Ore treated		Blister		Electrolytic	
	Tons	Percent copper	Tons	Percent copper	Tons	Percent copper
Nkana Roan Antelope Mufulira Nchanga	2, 469, 196 2, 551, 161 1, 640, 401 47, 460	3. 53 3. 15 4. 59 4. 15	50, 126 68, 904 61, 669 1, 315	99. 41 99. 48 99. 44 99. 58	29, 654	99. 95
Total	6, 708, 218	3. 65	182, 014	99. 45	29, 654	99. 95

161

The article also contains limited descriptions of other copper occurrences in Northern Rhodesia.

COPPER

Peru.—Recovery of copper from ores produced in Peru showed little change in 1942 from the previous year; production aggregated 37,000 metric tons (preliminary figures) compared with 36,822 tons in 1941. There is little expectation that a noteworthy increase in production will take place in 1943, the continuation of the 1942 rate even being dependent on the maintenance of a reasonable flow of supplies and equipment from the United States. The best chance for enlarged production is said to be at the Yauricocha mine of the principal company, the Cerro de Pasco Copper Corporation, but such an increase would depend on the receipt of equipment additional to that mentioned previously. The output of the principal mines in 1941 and 1942 is shown in the following table.


Copper produced by the principal mines in Peru, 1941-42

		1941		1942 1		
Company	Concen- trates			Concen- trates	Copper	
	or ores (metric tons)	Metric tons	Percent	or ores (metric tons)	Metric tons	Percent
Cerro de Pasco Copper Corporation: Casapalca concentrator Mahr concentrator	6, 232 <b>2, 644</b>	1, 299 546	20. 84 20. 65	4, 734 3, 364	1,118 635	23. 62
Morococha concentrator	30, 497 388, 138 4, 676	6, 737 12, 537 1, 509	22. 09 3. 23 32. 27	25, 035 448, 637 7, 776	5, 695 15, 119 2, 548	22. 7. 3. 3' 32. 7'
Soc. Min. Puquicocha Northern Peru M. & S. Co Do	13, 442 13, 280	3, 533 4, 683	26. 28 35. 26	10, 781 10, 804 2 560	3, 199 3, 775 324	29. 67 34. 94 57. 86
Cia, Minera Rescate	5, 771	1, 595	27.64	1,768	481	27. 2
		32, 439			32, 894	

<sup>1</sup> Preliminary.

The above companies produce roughly 90 percent of the total. Sweden.—According to reports, the Boliden Mining Co., outstanding producer in the country, is planning to increase its copper production to 18,000 metric tons annually, over double the 1938 rate. pyrites, copper, and zinc have been found in the company mines at Langsele, but so far no mining has been started. Ores rich in iron pyrites and having a low copper content have been discovered and surveyed at Asen and Svansele, but no mining has been done. Bjurfors the company is mining copper pyrites; the annual production is about 70,000 tons. The company also operates the Laver copper mine near Alvabyn in the Province of Norrbotten, from which copper concentrates are transported by truck and railway to the Rönnskär At Kristineberg, in the Skellefte district, about 430,000 tons of crude sulfide ore are mined annually, from which copper, zinc, and pyrite concentrates are obtained. Efforts to increase domestic production of copper from ores and scrap materials are believed to have left Swedish supplies notably below consumption requirements.

<sup>&</sup>lt;sup>2</sup> Cement copper.



# LEAD 1

# By T. H. MILLER AND A. L. RANSOME

### SUMMARY OUTLINE

	Page	for August San August San	Page
General summary	163	Stocks—Continued.	
Salient statistics	164	Consumers' stocks	171
War agency regulations	164	Domestic consumption	171
Domestic production	165	New supply	171
Primary lead	166	Consumption	172
Refinery production	166	Prices	173
Sources of primary lead	166	Foreign trade	173
Antimonial lead	167	Imports.	174
Secondary lead.	167	Exports	175
Lead pigments	168	World aspects of lead industry.	176
Mine production	168	World production	177
Stocks	170	Review by countries	177
Producers' stocks	170		111

## GENERAL SUMMARY

Record-breaking receipts of foreign lead in 1942 coupled with a fairly steady rate of domestic production, accomplished despite rising costs, eased the supply situation which was outstanding in comparison with other strategic materials and completely reversed the 1941 position relative to supply versus demand. The growing availability of lead under Government control measures permitted partial relaxation of these measures; this allowed increased use of the metal as a substitute for more critical materials, principally copper and

zinc, that have a more direct military application than lead.

The production of refined primary lead from domestic and foreign ores decreased less than 1 percent in 1942, the over-all total from both sources being only 4,128 tons less than the 1941 output. Although consumption of refined soft lead was less in 1942, it exceeded domestic production but permitted most of the imports of metal to be retained in the Government stock pile which at the end of 1942 was 13 times as large as at the beginning. Year-end stocks at domestic refineries advanced and reversed a 7-year downward trend, but consumers' inventories were 22 percent lower owing to the nonrelease of enough foreign metal to balance the deficient supply from domestic refineries.

Total imports of lead in all forms during 1942 again broke all records largely because of a 35-percent increase in receipts of refined lead over 1941; more than half of the increase came from Mexico and

the balance almost entirely from Australia, Canada, and Peru.

The established price of 5.85 cents a pound for lead at New York at the beginning of 1942 advanced to 6.50 cents on January 13, at which level it remained during the balance of the year; the average price for the year increased from 5.79 cents in 1941 to 6.48 cents in 1942.

THE PARTY OF THE P

<sup>&</sup>lt;sup>1</sup>.This report deals primarily with the smelting, refining, and consuming phases of the industry. For details of mining operations see separate reports issued for the various States.

Salient statistics of the lead industry in the United States, 1925-29 (average) and 1938-42, in short tons

	1925–29 (average)	1938	1939	1940	1941	1942
Production of refined primary lead:						
From domestic ores and base bullion	660, 525	331, 964	420, 967	433, 065	470, 517	467, 367
From foreign ores and base bullion	123, 104	51, 705	63, 068	100, 114	100, 450	99, 472
	783, 629	383, 669	484, 035	533, 179	570, 967	566, 839
Recovery of secondary lead	280,000	224, 900	241,500	260, 346	397, 416	323, 001
Imports: 1 Lead in pigs, bars, and old	4, 592	3, 235	7, 139	151, 568	274, 395	369, 254
Lead in base bullion	95, 747	15, 296	48,902	19, 624	24, 704	37, 244
Lead in ores and matte	40,096	45, 370	30,842	111,300	82, 115	81,936
Exports of refined pig leadLead remaining in bonded warehouse at	98, 048	45, 866	74, 392	<b>\$ 49, 079</b>	14, 359	* 5, 814
end of period	136, 969	87, 811	79, 215	211,876	156, 286	(4)
Refined primary lead available for con-			1 1	5		
sumption	690, 916	339,708	415, 031	633, 989	830, 797	927, 522
Estimated consumption of primary and	900, 250	546,000	667,000	782, 000	1,050,000	(4)
secondary leadPrices:	300, 200	040,000	001,000	102,000	1,000,000	
New York:			100			
Average for year_cents per pound	7.47	4.74		5. 18	5.79	6.48
Quotation at end of yeardo London averagedo	6. 25 5. 87	4.85 3.33	5. 50 3. 09	5. 50 (6)	5.85	6. 50 (6)
Mine production of recoverable lead	664, 230	369, 726	413, 979	457, 392	461, 426	496, 239
World smelter production of lead	1,850,000	1,874,000	1,911,000	(4)	(4)	(4)

Data include lead imported for immediate consumption plus material entering the country under bond.
 Includes 25,324 tons of foreign refined lead re-exported, according to American Bureau of Metal Statistics; official figures not available.

S Includes 3,874 tons of foreign lead re-exported, according to records of the Department of Commerce.

Data not available.

A verage for 8 months; London Metal Exchange dealings suspended for duration of war.
 Official maximum price fixed by British Ministry of Supply at £25 per long ton.

Figure 1 shows trends in the domestic lead industry since 1900. War agency regulations.—Throughout 1942 lead remained under full priority control according to General Preference Order M-38 originally announced in October 1941 and later extended beyond the March 1942 termination date. The order provided for a system of allocation that previously had been restricted to releases of foreign lead purchased and held by the Metals Reserve Co., and a "pooling" arrangement was set up whereby primary producers set aside 15 percent of current output each month for allocation to meet special needs. The subsequent easing of the lead situation eliminated the need for this plan later in 1942, and the emergency 15-percent "pool" was dropped after July until further notice, according to Supple-

mentary Order M-38-j effective July 4. Under Conservation Order M-38-c, issued January 10, 1942, uses of lead were divided into three classes: A prohibited list, an unlimited list, and all other uses limited to 90 percent of the 1941 consumption In September 1942 when the shortage was less acute industry requested some modification of the conservation order, but not until November 11, 1942, and again on January 1, and again on February 2, 1943, were amendments to the order issued that somewhat liberalized the use of lead for construction purposes and as a substitute for more critical materials, such as tin, brass, and bronze. Likewise, Limitation Order L-180, affecting storage batteries, was amended January 5, 1943, to balance consumption with available production of antimonial Despite the continued requests for freer use of lead, further liberalization of the conservation program is limited by the orders and conservation measures that affect other more critical metals. LEAD 165

(京) 大学大学

In an effort to stimulate domestic mine production the Office of Production Management, jointly with the Office of Price Administration, on January 13, 1942, announced the details of a premium-price plan whereby producers (miners) of lead (copper and zinc were also included in the plan) received, through the Metals Reserve Co., 9.25 cents a pound for lead produced in excess of quotas based on 1941 output as against the ceiling price of 6.50 cents a pound, New York, established on the same date. This plan, effective February 1, 1942, covered a period of 2½ years. In the Tri-State district a premium of \$39.60 (later adjusted to \$41.80) per ton for 80-percent lead sulfide




FIGURE 1.—Trends in the lead industry in the United States, 1900-1942. Imports include lead in ore, base bullion, pig lead, and scrap; exports include pigs, bars, and scrap lead exported in manufactures with benefit of draw-back.

concentrates was established for overquota production; this was equivalent to 2.75 cents per pound premium. The premium-price plan was continued without further change throughout 1942. On February 18, 1943, the scope of the Metals Reserve Co. plan was broadened to include an additional premium of 2.75 cents a pound, and the effective time limit was extended to July 31, 1945. Under the revised plan the highest possible payment for excess production amounted to 12 cents a pound, New York basis, depending upon the quotas assigned to the particular mine.

# DOMESTIC PRODUCTION

Pig lead is produced at primary plants that treat ore and a small amount of scrap and at secondary plants that treat scrap exclusively. Both types of plants may produce refined lead or antimonial lead. Because of the large quantity of battery scrap treated at secondary

smelters, their output is essentially antimonial-lead alloys. for production of refined lead at secondary plants are given in the section on Secondary Lead.

The following table shows production of refined lead and antimonial

lead at primary refineries from 1938 through 1942.

Refined lead and antimonial lead produced at primary refineries in the United States, 1938-42, in short tons

Year	From domes- tic ores and base bullion	From foreign ores and base bullion	From scrap	Total	Antimonial lead
1938. 1939. 1940. 1941. 1942.	331, 964 420, 967 433, 065 470, 517 467, 367	51, 705 63, 068 100, 114 100, 450 99, 472	24, 800 29, 011 16, 588 13, 454 12, 856	408, 469 513, 046 549, 767 584, 421 579, 695	24, 123 21, 995 29, 762 40, 237 51, 762

#### PRIMARY LEAD

Refinery production.—Production of refined primary lead decreased less than 1 percent in 1942.

Refined primary lead produced in the United States, 1938-42, by classes and sources

		Pro	duction (s	hort tons) b	<b>y</b> —		То	tal product	ion 1
		Class			Source			v	alue
Year	Desilver-	Soft	lead 3	From domestic	From	From	Short	Average	coloniated
	ized lead 1 3	Desil- verized	Undesil- verized	ores and base bul- lion	foreign ores	foreign base bullion		sales price per pound	
1938 1939 1940 1941	243, 891 280, 356 336, 456 366, 385 343, 971	31, 986 65, 349 43, 400 39, 872 42, 094	107, 792 138, 330 153, 323 164, 710 180, 774	331, 964 420, 967 433, 065 470, 517 467, 367	32, 862 24, 652 83, 563 74, 166, 81, 485	18, 843 38, 416 16, 551 26, 284 17, 987	383, 669 484, 035 533, 179 570, 967 566, 839	\$0.046 .047 .050 .057	\$35, 298, 000 45, 499, 000 53, 318, 000 65, 090, 000 71, 422, 000

Sources of primary lead.—Of the total refined primary lead produced in 1942, 82 percent was derived from domestic ores and base bullion and 18 percent from foreign, the same ratio as in 1941. Production from foreign ores increased 10 percent to within 2 percent of the record established in 1940, but lead refined from foreign base bullion was 32 percent less. The marked drop in output of lead from Mexican base bullion is due to larger quantities of bullion being refined in Mexico and does not indicate a corresponding decrease in total Mexican output of lead. This loss was offset in part by a marked increase in base bullion from Australia. Details of the sources of lead from domestic ores are given in the section on Mine Production.

Lead content of antimonial lead excluded.
 Desilverized soft lead excluded.
 Includes lead derived from Missouri ores and other nonargentiferous ores.

Refined primary lead produced in the United States, 1938-42, by sources, in short tons

Source	1938	1939	1940	1941	1942
Domestic ore and base bullion	331,964	420, 967	433, 065	470, 517	467, 367
Foreign ore: Australia. Canada. Europe. Mexico. South America. Other foreign.	7, 320 - 3, 562 - 14 - 9, 745 - 9, 887 - 2, 334	7, 580 4, 763 188 227 8, 869 3, 025	14, 856 9, 009 3, 650 1, 303 34, 744 20, 001	19, 561 5, 708 123 390 27, 173 21, 211	19, 638 5, 980 14 2, 403 23, 127 30, 323
	32, 862	24,652	83, 563	74, 166	81, 485
Foreign base bullion: Australia Mexico South America Other foreign	18, 268	37, 463 9 944	16, 161	831 25, 358 47 48	16, 902 111 216 758
	18, 843	38, 416	16, 551	26, 284	17, 987
Total foreign	51,705	63,068	100, 114	100, 450	99, 472
Grand total	383, 669	484, 035	533, 179	570, 967	566, 839

Antimonial lead.—Antimonial or hard lead is an important byproduct of the refining of base bullion, but the quantity derived from this source is only a small part of the country's annual production. The greater part is obtained from the smelting of antimonial-lead scrap, and some is produced by mixing metallic antimony with refined soft lead.

Production data from lead-smelting plants that handle scrap materials exclusively are summarized in the following section and discussed in detail in the chapter on Secondary Metals—Nonferrous. A large quantity of hard-lead scrap also is treated at primary smelters and refineries; the production of antimonial lead at such plants is shown in the following table. Since 1939 production has increased steadily, but in general the percentage of antimony contained has declined correspondingly.

Antimonial lead produced at primary lead refineries in the United States, 1938-42

	Production	Antimon	y content	Lead c	content by difference (short tons)			
Year	(short tons)	Short tons	Percent	From do- mestic ore	From foreign ore	From scrap	Total	
1938	24, 123 21, 995 29, 762 40, 237 51, 762	2, 809 2, 031 2, 944 3, 510 3, 524	11. 6 9. 2 9. 9 8. 7 6. 8	6, 759 4, 117 7, 364 14, 852 24, 512	3, 385 3, 189 3, 023 8, 013 12, 165	11, 170 12, 658 16, 431 13, 862 11, 561	21, 314 19, 964 26, 818 36, 727 48, 238	

### SECONDARY LEAD

Although some scrap lead is treated at primary plants, the major portion is refined at a large number of plants that operate exclusively on secondary materials. Secondary lead is recovered in the form of refined lead, antimonial lead, other alloys, and chemicals. Recovery at primary and other plants in 1941 and 1942 is shown in the following table. Secondary lead recovered in 1942 was 19 percent less than in 1941 and was equivalent to 69 percent of the domestic refined primary

Further details appear in the chapter on Secondary lead output. Metals—Nonferrous.

Secondary lead recovered in the United States, 1941-42, in short tons

	1941	1942
As refined metal:		
At primary plants At other plants	 13, 454 61, 810	12, 856 55, 746
	75, 264	68, 602
In antimonial lead: At primary plants At other plants	13, 862 192, 660	11, 561 158, 998
In other alloys 1	206, 522 115, 630	170, 559 83, 840
Grand total: Short tons Value	 397, 416 \$45, 305, 400	323, 001 \$40, 698, 100

<sup>1</sup> Includes some lead in chemical compounds.

### LEAD PIGMENTS

Lead pigments manufactured in 1942 contained 223,338 tons of lead—an 18-percent decrease from 1941. Of the 206,680 tons of lead in pigments derived from refined pig lead, litharge contained 42 percent, white lead 36 percent, red lead 22 percent, and sublimed lead, leaded zinc oxide, and orange mineral less than 1 percent. Leaded zinc oxide and sublimed lead are the principal pigments of which the lead content is derived from ores. Details of production and consumption of lead pigments are given in the chapter on Lead and Zinc Pigments and Zinc Salts.

Lead in pigments produced in the United States, 1938-42, by sources, in short tons 1

Year	Lead in pigments from—					Lead in pigments from—				
	Ore		Year	Ore						
	Domes-	Foreign	Metal	Total		Domes- tic	Foreign	Metal	Total	
1938 1939 1940	12, 025 15, 171 16, 869		163, 815 200, 390 196, 235	175, 840 215, 561 213, 104	1941 1942	23, 951 15, 949	290 707	248, 674 206, 680	<sup>2</sup> 273, 315 <sup>2</sup> 223, 338	

Includes also lead recovered in leaded zinc oxide.
 Includes 400 tons from scrap.
 Includes 2 tons from scrap.

# MINE PRODUCTION

Mine production of lead (including that made into lead pigments) in the United States and Alaska increased 8 percent in 1942, the advance being credited to an over-all gain of 4 percent in the Western States and Alaska and 12 percent in the Central States, which more than compensated for a decline of 19 percent in the Eastern States. Production of lead from southeastern Missouri increased 33,090 tons to a total of 197,432 tons, or about 40 percent of the entire United

States production. The output from the Tri-State region amounted to 34,341 tons, a drop of 6,739 tons and a reversal of the trend of 1941. A gain in southwestern Missouri was too small to balance losses in the greater productive States of Oklahoma and Kansas. Idaho continued to be the leading producer of the Western States with a 9-percent increase, followed by Utah and Montana with a 3-percent rise and 6-percent loss, respectively. The decrease in Montana's total production of recoverable lead was due largely to the closing in May of nearly all the zinc-lead mines of the Anaconda Copper Mining Co. at Butte in favor of maintaining copper production in the face of labor shortages. Arizona produced 866 tons less than during the record year of 1941, largely because of the decline in output of zinclead ore from the Tennessee-Schuylkill mine at Chloride and the suspension in January of the milling of zinc-lead ore from the Hillside In Colorado and Washington the recoverable mine production of lead continued to gain, but the output from Nevada, largely from the Pioche district, and from New Mexico declined. Additional details of production by mines, districts, and States may be found in the State chapters.

Mine production of recoverable lead in the United States, 1925-29 (average) and 1938-42, by States, in short tons

State	1925-29 (average)	1938	1939	1940	1941	1942
Western States and Alaska:						
Alaska	982	994	937	779	662	415
Arizona	9, 743	10, 571	10, 771	13, 266	15, 638	14, 772
California	2,070	495	526	1,772	3, 464	5. 151
Colorado	30, 112	9, 455	8, 222	11, 476	12, 574	15, 181
Idaho	141, 610	92, 177	90, 981	104, 834	104, 914	113, 909
Montana	18, 871	9, 327	16, 555	23, 036	21, 259	20, 050
Nevada	9, 807	4, 679	4, 236	7, 499	9, 623	5, 376
New Mexico	6, 730	4, 949	5, 392	3, 822	4, 668	4, 608
Oregon.	0,700	23	15	35	59	23
South Dakota	21	20	10	7	00	85
Texas	213	342	227	205	186	181
Utah	149, 509	65, 657	67, 634	75, 688	69, 601	71, 930
Washington	1, 323	4. 284	3, 718	2,555	3,903	4, 851
Wyoming	1,020	1, 201	0, 110	2,000	9, 900	3,001
w yoming						
	370; 997	202, 953	209, 214	244, 974	246, 551	256, 535
<u>.</u>						
Central States:			*.	1		1. 4/4 1.00
Arkansas	38	7		55	11	2
Illinois	552	175	308	1,508	2, 376	2, 344
Kansas	26, 121	15, 239	13, 697	11,927	14,538	9, 419
Kentucky	135	101	87	360	282	335
Missouri	202, 240	122, 027	156, 281	172,052	165, 909	199, 548
Oklahoma	58, 306	21,004	27, 720	21, 240	25, 021	22, 806
Wisconsin	1, 745	320	388	445	1, 225	775
	289, 137	158, 873	198, 481	207, 587	209, 362	235, 229
Eastern States:						
New York		2,005	2, 387	1,973	2,100	2, 434
Tennessee	250	553	517	573	23	238
Virginia	3,846	5, 338	3, 380	2, 285	3, 390	1,803
North Carolina		4				
	4, 096	7, 900	6, 284	4, 831	5, 513	4, 475
	664, 230	369, 726	413, 979	457, 392	461, 426	496, 239

Mine production of recoverable lead in the United States, by districts that produced 1,000 tons or more during any year from 1938 to 1942, in short tons

District	State	1938	1939	1940	1941	1942
Southeastern Missouri re-	Missouri	118, 870	153, 522	169, 893	164, 342	197, 291
Coeur d'Alene region	Idaho	82, 274	81, 699	95, 609	95, 529	106, 474
Bingham	Utah	41, 334	36, 842	37, 857	34, 512	39, 996
Joplin region		39, 400	44, 176	35, 311	41, 080	34, 341
Park City region	Utah	7, 258	11, 631	19.749	19.094	15, 278
Tintic	do	9,605	8, 618	6, 536	9, 424	10, 176
TinticButte	Montana	204	4, 708	8, 859	8, 630	7, 206
Harshaw	Arizona	149	2, 287	4, 581	5, 541	6, 132
Metaline	Washington		3, 509	2, 495	3, 819	4, 553
Resting Springs	California		0, 000	2, 495 870	2, 581	4, 044
Rush Vallev	Track		0 400			3, 988
	Utah	4,619	3, 422	4, 760	4, 168	
Warm Springs	Idaho	7, 370	5, 565	5, 050	5, 334	3, 783
Leadville	Colorado	1, 222	1,088	794	1, 112	3, 348
Central	New Mexico	340	2, 941	3, 245	3, 902	3, 206
Pioche	Nevada	3, 214	2, 964	5, 520	6, 822	2, 764
St. Lawrence County	New York	2,005	2, 387	1, 973	2, 100	2, 434
Heddleston	Montana		7	50	967	2, 290
Pioneer (Rico)	Colorado	29	752	1,928	2, 525	2, 282
Red Cliff	do	933	1, 137	1,412	1,710	2, 240
Animas	do	996	958	2, 471	3, 045	2, 124
Eagle	Montana	4, 301	3, 252	4, 108	3, 294	1, 999
Smelter	do	710	1, 256	1, 363	1. 527	1, 988
Old Hot	Arizona	1.919	1, 861	1,908	2, 172	1, 801
Old HatUpper San Miguel	Colorado	885	1, 489	1, 278	1, 408	1,716
Opper San Wilguel	Montana	283	780	131	1, 408	1, 704
				1 2, 285	3, 390	
Austinville	Virginia	5, 338	3, 380			1,661
Wallapai	Arizona	4,004	703	2, 304	2, 408	1,656
Bayhorse	Idaho	915	999	935	1,378	1,644
Ophir	Utah	2, 013	6, 050	5, 354	1, 437	1, 623
Port Hill	Idaho	291	1, 111	1,837	1, 537	1,044
Montana	Montana	212	293	955	1,601	1, 025
Upper Mississippi Valley.	and Wisconsin.	320	388	453	1, 345	908
Hog Heaven	Montana	1, 214	2, 767	3, 588	2, 824	614
Cataract	do	1, 326	1,672	1,904	355	26
Oro Blanco	Arizona	4, 150	3, 568		1	6
Willow Creek	New Mexico	4, 277	1, 800			<del>-</del>

<sup>&</sup>lt;sup>1</sup> Total for Virginia but almost entirely from Austinville district.

## STOCKS

Producers' stocks.—Lead stocks, as reported by the American Bureau of Metal Statistics, are shown in the following table. Stocks of refined and antimonial lead include metal held by all primary refiners and by most refiners of secondary material who produce common soft lead. Foreign lead refined in the United States and entered for domestic consumption is included.

Lead stocks at end of year at smelters and refineries in the United States, 1938-42, in short tons

The state of the s					
	1938	1939	1940	1941	1942
Refined pig leadAntimonial lead	102, 489 13, 413	52, 783 5, 994	32, 458 8, 468	15, 973 4, 212	28, 815 6, 122
	115, 902	58, 777	40, 926	20, 185	34, 937
Lead in base bullion— At smelters and refineries. In transit to refineries In process at refineries.  Lead in ore and matte and in process at smelters.	18, 693 2, 339 16, 690 37, 722 56, 332 209, 956	10, 337 3, 521 15, 958 29, 816 59, 486 148, 079	9, 166 3, 457 18, 141 30, 764 71, 722 143, 412	8, 594 2, 215 17, 709 28, 518 51, 446 100, 149	7, 359 1, 706 13, 925 22, 990 59, 247

171 LEAD

THE PARTY OF THE PROPERTY OF THE PARTY OF TH

In contrast with 1941 the excess of production over shipments in 1942 resulted in an over-all gain in inventories for the year. of refined and antimonial lead at refineries, which totaled approximately 20,200 tons at the end of 1941, steadily increased to 31,400 tons by the end of April, followed by a general decline to 25,900 tons by the end of August. During the next 3 months increasing output more than balanced nearly constant shipments, and stocks advanced to 35,600 tons by the end of November—the high point for the year. A slight decrease in output in December coupled with a gain in shipments reduced inventories to about 35,000 tons at the end of 1942, a net gain of 73 percent over the total on hand at the end of 1941. Stocks of lead in ore and matte and in process at smelters, in base bullion at smelters and refineries, and in transit to and in process at refineries were 3 percent higher at the end than at the beginning of 1942.

Consumers' stocks.—The data on consumers' stocks by grades at the beginning and end of 1942 are shown in the following table. These results, as obtained from a consumer survey of 500 respondents, are estimated to represent 85 to 90 percent of the consuming industry on the basis of lead consumed, but the same relative percentage does not necessarily hold as regards inventories. Stocks of all grades of domestic lead decreased slightly, but the decided drop in foreign lead caused an over-all decline of 22 percent by the end of 1942.

Consumers' stocks of refined soft lead at beginning and end of 1942, by grades, in short tons 1

	Domestic			Foreign (all	Total	
	Corroding	Chemical	Common	grades)	100ai	
Dec. 31, 1941 2	29, 900 25, 532	17, 456 16, 587	32, 363 31, 360	21, 245 5, 587	100, 964 79, 066	

Based upon a survey of 500 respondents.
 Revised figures.

# DOMESTIC CONSUMPTION

New supply.—The calculated supply of refined primary lead available for consumption in 1942 was 12 percent above that for 1941 and 34 percent above the 1925-29 average (690,916 tons). The figures in the following table do not include variations in producers' stocks and do not indicate the true trend in actual consumption. Moreover, the greater part of the large tonnage of imported lead which swelled the supply in 1942 is still held in Government stock piles.

Refined primary pig lead available for consumption in the United States, 1938-42, in short tons

	1938	1939	1940	1941	1942
Supply: Imports Production	1, 905	5, 388	149, 889	274, 189	366, 497
	383, 669	484, 035	533, 179	570, 967	566, 839
Withdrawn: Exports	385, 574	489, 423	683, 068	845, 156	933, 336
	1 45, 866	74, 392	2 49, 079	14, 359	3 5, 814
Supply available for consumption	339, 708	415, 031	633, 989	830, 797	927, 522

<sup>&</sup>lt;sup>1</sup> Includes small quantity of "sheets and pipes"; figures not separable.
<sup>2</sup> Includes 25,324 tons of foreign refined lead re-exported, according to American Bureau of Metal Statistics; official figures not available.
<sup>3</sup> Includes 3,374 tons of foreign refined lead re-exported, according to records of the Department of Com-

Consumption.—Although figures showing the total consumption of lead, primary and secondary (including antimonial lead), are not available for 1942 the total probably was somewhat less than the record 1,050,000 tons consumed in 1941 as reported by the American Bureau of Metal Statistics. Owing to the return of large quantities of secondary lead in discarded and obsolete articles and from the lead-consuming industries, the total consumption of pig lead greatly exceeds the supply of new lead. The supply of new lead was greater in 1942, but the actual tonnage released to consumers was considerably less because of use restrictions, and the proportion of secondary and scrap lead to primary material was probably even higher than normal.

Consumption of refined soft lead in the United States, 1941-42, by grades and uses, in short tons 1

	1941	1942		1941	1942
By grades: Domestic: Corroding	289, 679 150, 206 257, 113 115, 649	227, 207 142, 213 134, 101 92, 568 596, 089	By uses—Continued. Collapsible tubes	3, 726 51, 516 32, 946 35, 480 35, 630 73, 982 2, 069	9, 966 9, 375 21, 395 31, 774 34, 764 41, 135 2, 337
By uses: Ammunition Bearing metals Cable covering Calking lead Casting metals	32, 959 10, 160 141, 161 32, 380 9, 243	48, 025 12, 648 113, 374 9, 038 3, 074	Type metals	2, 975 83, 230 143, 496 8, 861 112, 833 812, 647	943 58, 372 98, 667 6, 298 94, 904 596, 089

<sup>&</sup>lt;sup>1</sup> Based upon survey of 500 respondents; 1941 figures are revised, but 1942 figures are preliminary and subject to revision.
<sup>2</sup> Includes consumption of lead in manufacture of tetraethyl lead, lead used for ships' ballast, annealing, galvanzing, brass and bronze, and other miscellaneous uses.

A consumer survey conducted by the Bureau of Mines for the second consecutive year disclosed that the consumption of refined soft lead at 500 plants decreased 27 percent in 1942. Judging from available data as regards supply, shipments, and producers' stocks, receipts of 607,431 tons of refined soft lead by those consumers canvassed indicate that the 1942 coverage was probably 85 to 90 percent. Antimonial lead, unrefined scrap lead, and lead in alloys are not The accompanying table presents a 2-year comparison by grades and by uses of soft lead. Consumption of all three grades of domestically refined lead and foreign lead declined, common lead showing the greatest drop (48 percent). Of the total amount used in 1942 (comparative 1941 percentages in parentheses), corroding accounted for 38 (36) percent, chemical 24 (18) percent, common 23 (32) percent, and all grades of foreign 15 (14) percent. Consumption of lead by uses decreased during 1942 except that consumed in making ammunition, bearing metals, collapsible tubes, and terne-Use in solder remained virtually unchanged. Cable covering was the largest of the principal uses of soft lead in 1942, followed in order by red lead, litharge, white lead, ammunition, and storage batteries. The effect of conservation measures, use restrictions, and the general industrial change-over from peacetime to wartime economy is particularly apparent with respect to some of the principal uses of lead. The cessation of automobile manufacturing largely was respon-

sible for the drop in the consumption of lead for storage batteries and, to some extent, the decline in lead used for red lead and litharge which also enters into the manufacture of batteries and pigments. White lead, the most widely used lead paint pigment, showed a considerable decline, and foil dropped markedly, largely owing to the restrictions placed on the consumption of lead in making foil for packaging.

# PRICES

The two major markets for lead in the United States are New York and St. Louis; much of the lead produced in this country is sold at prices normally based upon quotations in these markets. Since suspension of the London Metal Exchange dealings in September 1939 for the duration of the war the London market has had no actual influence on New York quotations, and the differential between St. Louis and New York prices has remained at 0.15 cent a pound, an amount approximating the freight charges between the two points.

At the beginning of the year prices for pig lead were 5.70 cents at St. Louis and 5.85 cents at New York, both prices having prevailed since March 26, 1941. Effective January 13, 1942, the Office of Price Administration established the ceiling price for lead at 6.35 cents, St. Louis, and 6.50 cents, New York, at which point it remained for the remainder of 1942.

The official London maximum price of £25 per long ton, duty paid, for Empire and foreign lead, as fixed by the British Ministry of Supply in December 1939, remained unchanged during 1942.

Average monthly and yearly quoted prices of lead at St. Louis, New York, and London, 1938-42, in cents per pound 1

	1940			1941			1942		
Month	St. Louis	New York	Lon- don	St. Louis	New York	Lon- don	St. Louis	New York	Lon- don
January February March April May June July August September October December December	5. 32 4. 93 5. 04 4. 92 4. 87 4. 85 4. 70 4. 78 5. 58 5. 35	5. 47 5. 08 5. 19 5. 02 5. 00 5. 00 4. 85 4. 93 5. 73 5. 50	(2)	5. 35 5. 45 5. 61 5. 70 5. 70 5. 70 5. 70 5. 70 5. 70 5. 70 5. 70 5. 70 5. 70	5. 50 5. 60 5. 77 5. 85 5. 85 5. 85 5. 85 5. 85 5. 85 5. 85 5. 85	(2)	6. 12 6. 35 6. 35 6. 35 6. 35 6. 35 6. 35 6. 35 6. 35 6. 35 6. 35	6. 27 6. 50 6. 50 6. 50 6. 50 6. 50 6. 50 6. 50 6. 50 6. 50 6. 50	(2)
Average	5.03	5. 18	(2)	5.64	5.79	(2)	6. 33	6.48	(2)

St. Louis: Metal Statistics, 1943, p. 465. New York: Metal Statistics, 1943, p. 457.
 London Metal Exchange dealings suspended for duration of war. Official maximum price fixed by British Ministry of Supply at £25 in December 1939.

# FOREIGN TRADE 2

The continued upward trend in imports of lead was most significant in 1942. The total receipts of foreign material, principally as refined metal but also as lead in ore, matte, and base bullion, were sufficient not only to supplement the domestic refinery production but also to allow reserve stock piling of a large tonnage of pig lead. The result

<sup>&</sup>lt;sup>3</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

of this increased supply, coupled with Government control, was to

place lead in the position of a substitute metal.

Imports.—Total imports of lead in 1942 again broke all records largely on account of a 35-percent increase in receipts of foreign refined lead over 1941. In this category Mexico furnished 52 percent, Australia nearly 23 percent, Canada 19 percent, and Peru 6 percent as compared with 36, 16, 33, and 15 percent, respectively, in 1941. Nearly all imports of base bullion (97 percent) in 1942 came from Australia, which heretofore has furnished little or no material of this class. Since the war, however, lead bullion in excess of that which could be refined in Australia has been shipped to the United States rather than to other metallurgical centers barred by wartime restrictions. Lead in ores and matte came from many countries but principally from Newfoundland, Australia, Peru, and Canada, which together supplied 81 percent of the total imports of this material.

Total lead imported into the United States, 1938-42, by forms in which imported, in short tons 1

Year	Lead in ore	Lead in base	Pigs, bars,	Total lead
	and matte	bullion	and old	content
1938	45, 370	15, 296	3, 235	63, 901
1939	30, 842	48, 902	7, 139	86, 883
1940	111, 300	19, 624	151, 568	282, 492
1941	82, 115	24, 704	274, 395	381, 214
1942	81, 936	37, 244	369, 254	488, 434

<sup>&</sup>lt;sup>1</sup> Data include lead imported for immediate consumption plus material entering country under bond.

Total lead imported into the United States, in ore, base bullion, and refined, 1938-42, by countries, in short tons <sup>1</sup>

Year	Canada	Mexico	Newfound- land	South America <sup>2</sup>	Europe	Other countries	Total
1938 1939 1940 1941 1942	3, 174 5, 641 8, 721 95, 686 77, 677	38, 467 52, 059 149, 493 129, 446 194, 820	27, 563 17, 569 26, 549	13, 426 16, 527 63, 120 69, 826 42, 263	680 1, 971 3, 891 175 52	8, 154 10, 684 29, 704 68, 512 147, 073	63, 901 86, 883 282, 492 381, 214 488, 434

<sup>&</sup>lt;sup>1</sup> Data include lead imported for immediate consumption plus material entering country under bond.

<sup>1</sup> Includes imports from Argentina as follows—1938: 4 tons; 1939: 3,362 tons; 1940: 16,469 tons; 1941: 13,374 tons; and 1942: 4,582 tons.

Total lead imported into the United States in ore, matte, base bullion, pigs, bars, and old, 1938-42, by countries, in short tons 1

Country	1938	1939	1940	1941	1942
In ore and matte:			:		
Africa	6, 434 3, 173 2, 107	7 3, 362 7, 612 7 5, 624 1, 844	7, 586 16, 469 17, 472 2, 707 8, 666 6, 271	575 13, 374 22, 634 7, 314 5, 725 1, 384	3, 871 4, 582 20, 997 1, 383 7, 468 3, 166
Mexico Newfoundland Peru	24, 023	3,846	1, 804 27, 563	5, 770 17, 569	2, 358 26, 549
United Kingdom Other countries	9,317 2 310	7, 174 1, 058 308	18, 383 3, 498 881	6, 665 175 930	11, 16
	45, 370	30, 842	111, 300	82, 115	81, 936

See footnote at end of table.

Total lead imported into the United States in ore, matte, base bullion, pigs, bars, and old, 1938-42, by countries, in short tons 1—Continued

Country	1938	1939	1940	1941	1942
In base bullion:				835	36, 289
Mexico	14, 444	47, 915	19,009	23, 726	56
PeruOther countries	198 654	84 903	179 436	58 85	16 883
	15, 296	48, 902	19, 624	24, 704	37, 244
In pigs, bars, and old: Australia	1, 475 1	2,727 17 298	4, 266 55 128, 680	43, 631 89, 887 99, 950	84, 749 70, 089 192, 4 <b>0</b> 6
Peru Other countries	1, 736 23	4, <b>0</b> 51 46	18, 452 115	<b>40,868</b> 59	21, 948 62
	3, 235	7, 139	151, 568	274, 395	369, 254
	63, 901	86, 883	282, 492	381, 214	488, 434

<sup>1</sup> Data include lead imported for immediate consumption plus material entering the country under bond.

Lead 1 imported for consumption in the United States, 1938-42, by forms in which imported

Year	dust, a	ores, flue nd mattes, s. p. f.		Lead in base bullion Pigs		Sheets, pipe, and shot			Not other-wise	Total value
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	speci- fied (value)	
1938 1939 1940 1941 1942	6, 722 12, 317 70, 027 82, 345 90, 633	\$543, 164 1, 063, 512 4, 659, 445 5, 343, 577 5, 685, 692	304 1,764 9,992 17,579 41,977	\$31, 147 166, 298 , 929, 946 1, 743, 350 3, 603, 026	2, 001 4, 772 36, 882 325, 999 388, 533	\$84, 109 176, 437 2, 269, 075 23, 403, 260 33, 091, 425	166 170 201 47 20	\$30, 906 28, 296 36, 444 15, 812 7, 009	\$23, 381 11, 611 12, 046 19, 389 4, 690	\$733, 081 1, 449, 541 7, 910, 873 30, 582, 741 42, 529, 235

<sup>&</sup>lt;sup>1</sup> In addition to quantities shown (values included in total values), "reclaimed, scrap, etc.," imported as follows—1938: 189 tons, valued at \$20,374; 1939: 36 tons, \$3,387; 1940: 24 tons, \$3,917; 1941: 1,331 tons, \$57,353; and 1942: 1,305 tons, \$137,393. Figures for 1942 include foreign lead received by the Government and held in stock piles.

Miscellaneous products, containing lead, imported for consumption in the United States, 1938-42

Year	Babbitt meta other com	al, solder, white binations contai	metal, and ning lead	Type met	Type metal and antimonial lead		
I ear	Gross weight (short tons)	Lead content (short tons)	Value	Gross weight (short tons)	Lead content (short tons)	Value	
1938	390 136 1, 368 702 972	77 45 429 241 274	\$126, 660 96, 492 1, 026, 432 711, 388 66, 096	433 380 1, 482 1, 657 245	374 321 1, 291 1, 454 210	\$38, 708 38, 491 108, 286 112, 120 19, 631	

Exports.—Total exports (excluding re-exports of foreign refined lead) of lead in 1942 were much less than in 1941. The marked drop from the high level of 1939 resulted from the restrictions imposed under the Export Control Act of 1940.

# Lead exported from the United States, 1938-42

Year	Pigs and bars		Foreign lead exported in		Pigs a	nd bars	Foreign lead exported in
	Short tons	Value	manufactures with benefit of draw-back (short tons)	Year	Short tons	Value	manufactures with benefit of draw-back (short tons)
1938 1939 1940	1 45, 866 74, 392 23, 755	1 \$3, 354, 616 4, 547, 219 1, 794, 590	9, 061 10, 379 15, 604	1941 1942	14, 359 1, 940	\$1, 159, 148 285, 354	21, 953 26, 248

<sup>1</sup> Includes sheets and pipes; figures not separable.

Pig lead exported from the United States, 1938-42, by destinations, in short tons

Destination	1938 1	1939	1940 *	1941	1942 3
Countries:					
Belgium	28	588	644		
Brazil		647	1,559	764	51
Canada		5	34	12	1
Chile		323	492	822	18
China		224	517	2, 335	
Denmark		1,569	112		
Finland		616 540			
France	(1)		1,120		
Germany		8, 333 560	437		
Hungary		34,790	11, 958	8, 154	
Japan	30, 203 314	99	336	0,102	
Kwantung	11, 403	2, 922	15	14	
Mexico	11,405	2, 101	2, 352	14	
		1,091	2, 002		
Norway Panama		238	538	379	74
Philippine Islands	1,037	974	450	628	
Sweden		7, 340	301	112	224
United Kingdom		9, 411	. 001		1, 379
Uruguay		0, 111	350	407	2,010
Other countries	821	2,021	2,538	732	186
Other Countries		2,021	2,000		
	45, 866	74, 392	23,755	14, 359	1,940
	10,000			,	
Continents:	1 '				
North America	12,002	3,345	865	574	134
South America		1,317	3,078	2, 334	192
Europe.		33, 152	6,400	228	1,608
Asia		36, 122	13, 384	11, 132	4
Africa and Oceania		456	28	91	2

# WORLD ASPECTS OF THE LEAD INDUSTRY

Since 1939 the lack of production data from many of the important lead-producing countries has precluded any official statement of world According to estimates published by the Metal Bulletin, London, world smelter production of lead in 1941 reached 1,770,000 metric tons, a slight gain over the 1940 estimate of 1,700,000 tons from the same source. Although no figures are available for 1942, it is doubtful if total smelter production has increased appreciably, if at The Bureau of Mines estimated that in 1942 the world mine production of lead (recoverable lead content) amounted to roughly 1,635,000 metric tons, an indication that production did not increase. Based on estimates by countries, about 80 percent of the world's supply of lead ore by the end of 1942 was controlled by, or available to, the United Nations.

<sup>&</sup>lt;sup>1</sup> Includes sheets and pipes; figures not separable.

<sup>3</sup> In addition, 25,324 tons of foreign lead were re-exported, according to American Bureau of Metal Statistics; official figures not available.

<sup>4</sup> In addition, 3,874 tons of foreign lead were re-exported, according to records of the Department of

Commerce.
4 Less than 1 ton.

World production of lead, 1937-42, in metric tons 1 [Compiled by B. B. Waldbauer]

China         * 1,500         (4)         (4)         (2)         (	Country	1937	1938	1939	1940	1941	1942
Belgium         93, 310         94, 170         82,000         *55,000         *20,000         (2)           Burma         77,728         80,166         77,7228         83,000         (2)			10, 200	14,000	12, 864	(2)	(2)
Belgium         93, 310         94, 170         82,000         *55,000         *20,000         (2)           Burma         77,728         80,166         77,7228         83,000         (2)	Australia	232, 198	226, 155	269, 590	\$ 275,000	(2)	(2)
Burma	Belgium	93, 310		82,000			
Canada         181, 182         181, 783         172, 880         199, 662         201, 976         221           China         * 1,500         (*)	Burma	77, 728					/25
China         \$ 1,500         (4)         (4)         (2)         (							221.170
Chosen	China		(4)	(4)		(2)	
Czechoslovakia.         4,300         (4)         (2)	Chosen	5 850	X	X		\ \sigma_{\alpha}\	\ \X
France.         37, 168         41, 753         42, 000         * 20, 000         * 10, 000         (2)           Germany *         162, 400         171, 700         181, 440         * 200, 000         * 225, 000         (2)           Austria.         10, 836         9, 280         181, 440         * 200, 000         * 225, 000         (2)           Greece.         5, 890         6, 050         4, 925         (2)         (2)         (2)         (2)           Hungary.         147         (4)         (5)         (6)         (7)         (2)	Czechoslovakia			X	2	1 1	🔀
Germany   162, 400   171, 700   181, 440   200, 000   225, 000   (2)   Austria   10, 336   9, 280   181, 440   200, 000   225, 000   (3)   Greece		27 168	41 752	49 000	* 20 000	810,000	1 23
Austria 10,836 9,280 10,050 223,000 (2) (2) Hungary 147 (3) (4) (5) (5) (2) (2) (2) (2) Hungary 1547 (4) (5) (6) (5) (7) (2) (2) (2) (2) Hungary 10,000 10,0	Gormany i	169 400	171 700	<b>`</b>	• 20,000	* 10,000	
Greece	A victorio	102, 400	1/1, /00	} 181. 440	\$ 200,000	3 225, 000	(2)
Hungary	Change			J	(0)		(
Indochina							
Italy							(3)
Japan					(2)		
Japan	Italy	38, 938					
Northern Rhodesia   568   277   163   (2)   (2)   (2)   (2)   (2)   (3)   (4	Japan	10,200					
Norway	Mexico	<sup>6</sup> 214, 653	6 273, 529	213, 675	191, 980		6 197, 019
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$					(2)	(2)	(2)
Poland         17, 587         19, 973         (1)         *23,000         *25,000         (2)           Rumania         6, 725         5, 655         5, 100         (2)         (2)         (2)           South-West Africa         1, 355         3, 214         4, 283         690         (2)         (2)           Spain         31, 973         31, 809         25, 991         45, 991         (2)         (2)           Tunisia         24, 758         23, 916         23, 421         (2)         (2)         (2)           U. S. S. R.         19         11         (2)         (2)         (2)         (2)           U. S. S. R.         555,000         (4)         (4)         75,000         (2)         (2)           United Kingdom         10, 313         10,000         (4)         (2)         (2)         (2)         (2)           United States (refined) 7         423, 232         330, 963         404, 257         468, 675         494, 126         497           Yugoslavia         4, 038         8, 646         10, 652         (2)         (2)         (2)			323	321	(2)	(2)	(2)
Poland         17, 587         19, 973         (4)         *23,000         *25,000         (2)           Rumania         6, 725         5, 655         5, 100         (2)         (2)         (2)           South-West Africa         1, 385         3, 214         4, 283         690         (2)         (2)           Spain         31, 973         31, 809         25, 991         45, 991         (2)         (2)           Tunisia         24, 758         23, 916         23, 421         (2)         (2)         (2)           U. S. S. R.         19         11         (2)         (2)         (2)         (2)           U. S. S. R.         *55,000         (4)         (4)         *75,000         (2)         (2)           United Kingdom         10, 313         10,000         (4)         (2)         (2)         (2)         (2)           United States (refined) 7         423, 232         330, 963         404, 257         468, 675         494, 126         497           Yugoslavia         4, 038         8, 646         10, 652         (2)         (2)         (2)	Peru	19,053	28, 478	24, 310	31, 131	34, 375	42, 246
Rumania         6, 725         5, 655         5, 100         (2)         (2)         (2)         (2)         (2)         (2)         (2)         (2)         (2)         (2)         (2)         (2)         (2)         (2)         (3)         (4)         (4)         25,000         (2)         (3)         (3)         (4)         (3)         (3)         (4)         (4)         (2)         (3)         (3)         (4)         (4)         (2)         (3)         (4)         (2)         (3)         (4)         (4)         (2)         (3)         (4)         (4)	Poland	17, 587	19, 973			\$ 25,000	
South-West Africa     1, 355     3, 214     4, 283     690     (2)       Spain     31, 973     31, 809     25, 991     45, 991     (2)     (2)       Tunisia     24, 768     23, 916     23, 421     (2)     (2)     (2)     (2)       Union of South Africa     19     11     (2)     (2)     (2)     (2)       U. S. S. R.     *55, 000     (4)     (4)     *75, 000     (2)     (2)       United Kingdom     10, 313     10, 000     (4)     (2)     (2)     (2)       United States (refined) 7     423, 232     330, 963     404, 257     468, 675     494, 126     497       Yugoslavia     4, 038     8, 646     10, 652     (2)     (2)     (2)	Rumania	6, 725	5, 655	`ź. 100	(2)		(2)
Spain         31,978         31,809         25,991         45,991         (2)         (2)           Tunisia         24,758         23,916         23,421         (2)         (2)         (2)           Union of South Africa         19         11         (2)         (2)         (2)           U. S. S. R.         255,000         (4)         (6)         275,000         (2)         (2)           United Kingdom         10, 313         10,000         (4)         (7)         (2)         (2)         (2)           United States (refined) 7         423,232         330,963         404,257         468,675         494,126         497           Yugoslavia         4,038         8,646         10,652         (2)         (2)         (2)	South-West Africa	1, 355					(2)
Tunisia         24,758         23,916         23,421         (2)						(2)	(2)
Union of South Africa. 19 11 (2) (2) (3) (3) U. S. S. R. 355,000 (4) (4) 375,000 (2) (2) (2) United Kingdom 10, 313 10, 000 (4) (2) (2) (2) (2) United States (refined) 7 423, 232 330, 963 404, 257 468, 675 494, 126 497 Yugoslavia 4, 038 8, 646 10, 652 (2) (2) (2) (2)	Timisia					25	(2)
U. S. S. R. 255,000 (4) (4) 275,000 (2) (2) (2) United Kingdom 10,313 10,000 (4) (2) (2) (2) (3) United States (refined) 7 423,232 330,963 404,257 468,675 494,126 497 (2) (2) (2) (2)	Union of South Africa	-1,.00			) }2	25	(2)
United Kingdom 10, 313 10, 000 (4) (2) (2) (2) (3) United States (refined) 7 423, 232 330, 963 404, 257 468, 675 494, 126 497 Yugoslavia 4, 038 8, 646 10, 652 (2) (2) (2)						2	2
United States (refined) 7 423, 232 330, 963 404, 257 468, 675 494, 126 497 Yugoslavia 4, 038 8, 646 10, 652 (2) (2) (2)		10 313		l X			
Yugoslavia	United States (refined) 7	423 232					497, 908
	Vinnelavia	4 029					397, 900
1 207 200 1 700 200 1 701 200 (2)	LUSUSIA VIALLELE	2,000	0,040	10, 002	(-)	(*)	(*)
1,681,000   1,700,000   1,734,000   (2)   (2)   (2)	1	1,681,000	1,700,000	1, 734, 000	(2)	(2)	(2)

By countries where smelted, but not necessarily refined.
 Data not yet available.
 Approximate production.
 Estimate included in total.

Exclusive of secondary material (Metallgesellschaft, Frankfort on the Main).

Includes small tonnage of lead contained in exported ore and concentrates. Separate figures not available.

7 Figures cover lead refined from domestic and foreign ores; refined lead produced from foreign base bullion not included.

#### REVIEW BY COUNTRIES

Argentina.—Production from the lead-zinc properties in the province of Jujuy came principally from the Aguilar mine of the Compania Minera Aguilar S. A., subsidiary of the St. Joseph Lead Co. output in 1942 was curtailed owing to a shortage of fuel oil. monthly production rate in January 1943 was estimated at 3,000 metric tons of lead concentrates. Total exports of lead concentrates (containing 74 percent lead, 6 percent zinc, and 50 ounces of silver) during January 1942 aggregated 1,950 metric tons; for the remainder of the year no further shipments were recorded. Stocks at the Aguilar mine and the port of Santa Fé on January 1, 1943, totaled 14,047 metric tons.

Australia.—Mining activities in Australia in 1942 were confronted with many adversities such as higher taxation, drafting of labor into the armed services, and flow of miners into higher paying munitions The Minerals Production Committee was authorized by the Federal Government to expedite the mining and treatment of strategic minerals by furnishing financial aid, providing equipment, and helping to alleviate manpower shortages; it also engaged in mining on its own account.

Production of lead concentrates was maintained at Mount Isa Mines, The Zinc Corporation, Ltd., reported lead lode ore reserves of 3,800,000 tons at the beginning of 1942.

Bolivia.—Mine production of lead in Bolivia, largely from small mines in the La Quiaca region, decreased from 15,653 metric tons (lead content in ore) in 1941 to 12,360 tons in 1942. All ore and concentrates are exported. No further information has been received regarding the erection of a lead smelter in the province of Sud Chichos. It was reported that such a plant would be built through the use of funds allotted by the Bolivian Banco Minero.

Brazil.—The Furnas mine in the Iporanga district continued to be the principal lead producer in 1942. Four additional deposits on the Iporanga River, operated by another company, are reported to have estimated reserves of 20,000 metric tons of galena. The State of São Paulo is having the mineral resources of this entire zone explored. The small lead smelter at Apiai, São Paulo, produced 10 tons of lead

during the year, all of which was consumed in Brazil.

Burma.—The Bawdwin lead-zinc mines of the Burma Corporation were seized by the Japanese near the end of April 1942. Assuming that the Japanese successfully repair the reported damage to mines, mill, and smelter, the potential peacetime annual output of about

80,000 tons of lead would become available to them.

Canada.—Production of lead in Canada increased from 230,084 short tons in 1941 to 255,751 short tons in 1942. These figures include smelter production plus lead contained in exported ore. Well over 95 percent of the lead is mined in British Columbia almost entirely from the Sullivan mine of the Consolidated Mining & Smelting Co. Sales of primary lead in Canada were placed under a system of control in 1942 whereby no producer could sell or supply primary or secondary lead or lead-base alloys in pig or ingot form without written approval of the Metals Controller of Canada; lead-base type metal, babbitt, and solder were excepted. Extensive exploratory drilling for new deposits was done in an effort to replace the heavy drain on existing reserves. Gulf Lead Mines, Ltd., was organized to continue the development of lead-zinc deposits on the east coast of Hudson Bay. Ore supplies are being supplemented by numerous efforts to recover lead from residues. The slag dumps at the gold mines of the Kirkland Lake and Larder Lake areas of Ontario yielded considerable lead, and the Western Exploration mill produced lead concentrates from tailings dredged from Slocan Lake. The New Calumet was expected to have its new 300-ton zinc-lead concentrator in operation before the end of 1942.

Mexico.—Mine production of lead in Mexico increased 27 percent from 155,259 metric tons (lead content of ore) in 1941 to 197,019 tons The most important event in 1942 was the Batemanduring 1942. Juarez-Tellez agreement between the Metals Reserve Co., the State Department, and the Mexican Government, under which the Metals Reserve Co. contracted to buy 250,000 tons of lead at 5.40 cents a pound each year for the duration of the war; the contract could be extended by mutual agreement after the war. Mexico agreed to stabilize taxes on lead, freeze freight rates, and hold in abeyance certain clauses in the labor laws. In spite of the agreement labor difficulties arose, and at the end of the year the miners were threatening to strike for a 25-percent wage increase. On December 23 a reciprocal trade pact with the United States reduced the duty on lead and lead in ore to 50 percent of the amount set by the United States Tariff Act of 1930. It will remain at this level until 30 days after

**LEAD** 179

Control of the second s

the termination of the national emergency, at which time it will be established at 20 percent below the rate set in the Tariff Act of 1930.

In 1942 the Avalos lead smelter of the American Smelting & Refining Co. at Chihuahua treated 466,549 metric tons of ore containing 118,401 tons of lead, compared with 362,211 tons of ore containing 94,947 tons of lead in 1941. Production from the five principal mines in the Chihuahua district increased in 1942, despite the fact that the Potosí Mining Co. exhausted its main ore body after nearly 100 years of operation. Nearly all the cooperative mining companies reverted to private ownership and operation in 1942. The Eagle Picher Lead Co. and the American Smelting & Refining Co. reopened old lead-zinc mines in the Taxco district. The El Bote mine, owned by the Sociedad Cooperativa Minera "El Bote", S. C. L., produced 30 tons of lead a day (content in concentrates).

Newfoundland.—The mine production of lead in terms of lead content of all concentrates produced amounted to 28,007 short tons in

1942 as compared with 33,166 tons in 1941.

North Africa.—The North African military campaign, starting in November 1942 and successfully concluded by the Allies in May 1943, aroused interest in raw materials thus made available to the United Nations. The largest lead producer in Morocco is the Aouli mine, 15 miles northeast of Midelt. Reserves at this property have been estimated at 60,000 tons on the basis of 75 percent lead concentrates. The concentrating plant has a capacity of 20 tons an hour.

The lead-mining industry in Tunisia is active; production comes from scattered deposits in the northern half of the country from ore (concentrates?) reportedly averaging 60 to 70 percent lead. In normal times about 90 percent of the Tunisian lead ores are treated at the smelter owned by the Peñarroya Co. at Mégrine, near Tunis, which has a capacity of about 25,000 metric tons of lead annually. On May 1, 1942, 3,700 tons of lead were in stock at the smelter. For the period January 1 to May 1, 1942, production of lead concentrates

in Morocco, Algeria, and Tunisia totaled 7,839 tons.

Peru.—The lead content of concentrates produced in Peru during 1942 was estimated to be about 55,830 metric tons, compared with 54,822 tons in 1941. This estimate is based upon the reports of companies producing 80 percent of the total lead output of Peru. Exports for 1942 included 3,117 metric tons of ore, 7,616 tons of concentrates, and 36,979 metric tons of refined lead compared with an estimated 8,000, 12,000, and 38,000 tons, respectively, in 1941. The largest lead producer is the Huaron mine; reserves are estimated to be 180,000 tons of positive ore and 500,000 tons of probable ore averaging 6.89 percent lead, 8.73 percent zinc, and 319 grams of silver per ton. The Oroya lead smelter, with a capacity to produce 4,000 tons of refined lead a month, recovered 42,246 metric tons of lead in 1942 (34,375 tons in 1941).

Spain.—According to the official figures of the General Mining Board of Spain, the 1942 output was 51,118 metric tons of lead concentrates compared with 43,728 tons in 1941. The most important deposits are in the Sierra Morena and the southeastern coast section. There are five lead smelters that reportedly can produce 32,000 to 35,000 tons of lead annually. Domestic consumption is about 23,000 tons, leaving a surplus of about 12,000 tons available for export.

Sweden.—The suspension of virtually all imports of lead in addi-

tion to other metals into Sweden due to the conditions of war has forced the Boliden Mining Co. to further intensify its efforts to produce the metal from Swedish deposits. Reportedly by the summer of 1943, the company will start commercial-scale production from the mine at Laisvall. Lead concentrates produced at this property have a lead content of 80 percent and are shipped to the Rönnskär smelter at Skelleftead.

# ZINC 1

## By A. L. RANSOME AND J. H. SCHAUM

## SUMMARY OUTLINE

	Page		Page
General summary	181	Domestic consumption	. 191
Salient statistics	182	New supply	. 191
War-agency regulations	182	Consumption	
Smelting capacity	183	Rolled zinc	
Supply of zinc concentrates	173	Prices	. 195
Domestic production	185	Zinc-reduction plants	. 196
Production of primary and redistilled sec-		Zinc smelters	. 196
ondary slab zinc	185.		
Distilled and electrolytic zinc	185	Foreign trade	. 197
Production of primary slab zinc by States	186	Imports	
Secondary zinc	187	Exports	. 198
Byproduct sulfuric acid	187	World aspects of zinc industry	
Zinc dust	187	World production	. 200
Zinc pigments and salts	188	Review by countries	. 200
Mine production	188		
Stocks	199		
Producers' stocks			
Consumers' stocks	191		

# GENERAL SUMMARY

In 1942, a year of broken records resulting from the "all-out" industrial mobilization of a nation at war, the zinc industry was outstanding in its ability to more than maintain the delicate balance between supply and demand. With the assistance of increasing Government regulatory measures, an expanded smelting industry increased its output 7 percent above the 1941 record to establish once more an all-time high level of production and to show a marked gain in stocks. Conservation measures restricting the use of zinc to essential needs resulted in an over-all 12-percent drop in domestic consumption, but consumers' stocks advanced 6 percent. The general decrease in domestic shipments of zinc by smelters was largely balanced by a gain in exports, principally for Lend-Lease accounts. The particular emphasis placed on the use of High-Grade zinc resulted in a 27-percent rise in production of high-purity metal, of which increasing amounts were made by redistillation of the lower grades of zinc. Partly as a result of this and also because of use restrictions, the lower grades of zinc decreased 8 percent. At the close of 1942, smelters were operating at usable capacity, with additional facilities under construction expected to bring an already enlarged output to a peak by the middle of 1943.

Domestic mine output showed only a slight gain in 1942 despite the incentive of premium prices, and to fulfill requirements and operate at capacity smelters continued to use foreign ore in greater amounts than ever before. Total imports in 1942 exceeded all previous records, as did domestic output of zinc from foreign ores, which amounted to 29 percent of the total production.

The established ceiling price of 8.25 cents a pound at St. Louis for Prime Western zinc was unchanged during 1942 and compares with

the average of 7.48 cents in 1941 and 6.34 cents in 1940.

のでは、日本は一大きな、いれば大いななないないできたがあるとうできない。これないできない。

The state of the s

<sup>&</sup>lt;sup>1</sup> This report deals primarily with the smelting branch of the industry. Full details of zinc mining are given in the various State reports. Some zinc ore is used directly in the manufacture of zinc pigments. (See chapter on Lead and Zinc Pigments and Zinc Salts.)

Salient statistics of the zinc industry in the United States, 1925-29 (average) and 1938-42

	1925–29 (average)	1938	1939	1940	1941	1942
Production of primary slab zine:						
By sources: From domestic oresshort tons_ From foreign oresdo	589, 648 12, 734	436, 007 10, 334	491, 058 16, 178	589, 988 85, 287	652, 599 169, 421	629, 957 261, 915
By methods:	602, 382	446, 341	507, 236	675, 275	822, 020	891, 872
Electrolytic percent of total Distilled do Production of redistilled secondary slab	21 79	21 79	25 75	28 72	27 73	28 72
zinc	43, 756	31, 613	50, 428	48, 917	59, 503	53, 195
short tons Primary zinc available for consumption	45, 575	157, 511	83, 728	19, 212	24, 212	82, 632
Price: short tons	548, 472	375, 004	607, 464	677, 168	762, 265	735, 865
Prime Western at St. Louis:  Average for yearcents per pound-	6. 76	4.61	5. 12	6.34	7.48	8. 25
Highest quotationdodo	8. 90 5. 40	5. 05 4. 00	6. 50 4. 50	7. 25 5. 50	8. 25 7. 25	8. 25 8. 25
Yearly average at London do Mine production of recoverable zinc	6. 46	3.05	1 2.89	(2)	(2)	(2)
Tri-State district (Joplin)	724, 720	516, 703	583, 807	665, 068	749, 125	768, 025
Western Statesdo	49 30	38 28	38 29	35 36	35 38	31 40
Other do do do World smelter production of zinc	21	34	33	29	27	29
short tons	1, 435, 000	1, 728, 000	1,800,000	1,810,000	(2)	(2)

Average for 8 months; London Metal Exchange dealings suspended in September.

2 Data not available.

## WAR-AGENCY REGULATIONS

Despite the excellent cooperation between the zinc industry and the Government during 1940 and 1941, the increasingly critical status of the over-all zinc supply problem necessitated more definite control Under General Preference Order M-11, in effect at the beginning of 1942, the War Production Board controlled the supply of slab zinc. However, this right was exercised over only a part of the total zinc output, as the percentage requirements for the "pool" increased from 31 in January to 75 of High Grade and 50 of lower grades in May, the balance of output being distributed by the industry. On May 1 Order M-11 was amended placing slab zinc under complete allocation effective June 1. A subsequent amendment on February 9, 1943, tightened the control on zinc by placing remelt zinc as well as refined metal under allocation. Because of the shortage of zinc dust for war purposes that developed at the end of 1942, this material, under the "pool" arrangement since June 1, was placed under complete allocation on December 22, 1942, according to General Preference Order M-11-l. Conservation Order M-11-b, issued July 24, restricted the use of zinc in a large number of manufactured products and prohibited others, the exceptions being principally for United States Government and Lend-Lease accounts. An amendment to this order prohibited the use of zinc after October 10 for making closures for glass containers, one of the largest peacetime uses of rolled A later amendment dated November 26 added to the list of prohibited items. Other restrictions were subsequently imposed by General Limitation Order L-71 as amended October 2, 1942, and amendment 1 to General Conservation Order M-99, which referred to production of dry-cell batteries and engravers' plates, respectively.

In an effort to increase domestic mine production, the Office of Production Management, jointly with the Office of Price Adminis**ZINC** 183

tration, on January 13, 1942, announced the details of a premiumprice plan whereby producers (miners) of zinc (copper and lead were also included in the plan) received, through the Metals Reserve Co., 11 cents a pound for zinc produced in excess of quotas based upon 1941 output as against the regular established ceiling price of 8.25 cents at East St. Louis. This plan became effective February 1, 1942, for In the Tri-State district the miner was paid an extra \$28.05 a ton for 60-percent concentrates, this being declared the equivalent of the 2.75 cents a pound premium. Later in the year the figure was adjusted to \$29.70. This plan was continued without further change in 1942, and although the expected increase in the rate of production did not materialize, the maintenance of past production was in itself an accomplishment. On February 18, 1943, Jesse Jones, Secretary of Commerce, announced that the scope of the Metals Reserve Co. premium-price plan had been broadened to include additional premiums and that the effective time limit had been extended to July 31, 1945. Under the revised plan two additional premiums for zinc were added, bringing the highest possible payment for excess production to a total of 16.50 cents a pound, East St. Louis basis, depending on the quotas assigned to the particular zinc mine.

Figure 1 shows trends in the zinc industry since 1900.

## SMELTING CAPACITY

Under the pressure of war requirements a record output of 945,067 short tons of slab zinc was produced from ore and secondary materials in 1942. This total is somewhat short of early estimates largely owing to delays in completing construction of additional smelting capacity caused by priority and manpower problems. The peak production scheduled for the latter part of 1942 will not be reached until well into 1943. By use of this additional capacity under construction it has been estimated that the 1943 production will reach 1,036,000 tons.<sup>2</sup>

An important development regarding zinc production in 1942 was the expansion of facilities for redistillation of the lower grades of zinc into High-Grade metal to supplement the already expanded existing plants that produce High-Grade zinc. This type of operation is

already being increased for 1943.

In all probability the scheduled total zinc productive capacity has reached the peak beyond which it will be impractical to go, the principal limiting factor being available supplies of zinc concentrates.

# SUPPLY OF ZINC CONCENTRATES

In 1942 the domestic mine production of recoverable zinc increased 2.5 percent over 1941—a notable achievement in view of the decline in quality of ore available for mining. Premium prices for overquota production stimulated the mining of high-cost ores, and although definite figures are not available it is safe to say that, to effect the small gain in output of recoverable zinc in 1942, a much larger gross weight of ore had to be mined than in 1941 because of the lower zinc content of the material milled.

In addition to production from mined ore, zinc was recovered from ever-increasing amounts of old tailings. The remilling of this lowgrade material, in many instances for the second and third time, was

<sup>&</sup>lt;sup>2</sup> As reported by American Zinc Institute, upon the basis of estimates by producer members that together represent approximately 98 percent of total United States production, including primary and secondary.

made possible by advances in milling technology plus the allowed premium payments for the zinc produced. Plants at Helena, Mont., and Tooele, Utah, added to the over-all supply in 1942 by treating lead blast-furnace slag for the recovery of zinc, and a third plant of this type, under construction in Idaho at the end of 1942, will be ready for operation in 1943.

An indicated decrease in production from domestic sources, to a large extent determined by a declining output from the Central States,




FIGURE 1.—Trends in the zinc industry in the United States, 1900–1942. Imports for consumption of slab and sheet zinc are not shown. Before 1936 they seldom exceeded 500 tons annually, but in recent years they have increased, amounting to 7,456 tons in 1938, 31,138 tons in 1939, 10,164 tons in 1940, 40,559 tons in 1941, and 36,445 tons in 1942.

makes the dependency on imports of foreign ores and concentrates greater than ever before. To keep smelters operating at their expanded capacity in 1942, it was necessary to import foreign material totaling an amount equal to 10 times that in 1939, and estimates of increasing imports for 1943 and 1944 indicate that zinc produced from foreign raw material will exceed the total metal output from domestic mines. The foreign supply, principally from the Western Hemisphere, comes largely from Mexico and Canada. Imports from these two countries, which supplied nearly two-thirds of the minimum import requirements in 1942, fortunately move by all-rail routes to

zinc 185

ころとのは、我のから人からればれるのはないないないないできます。

それが必要はないない あんかん かんかん こうしんかん

the United States and may be counted on for future supplies, with

nearly equal assurance as domestic production.

The United States has encouraged further development of foreign ore deposits by lending both technical and financial assistance to many mines in other countries through the auspices of the Board of Economic Warfare and the Metals Reserve Co. Definite contracts made by the latter agency for production and delivery of specific amounts have already resulted in gains in foreign output; assuming that necessary increases in water-borne imports can be relied upon, the minimum requirements for 1943 are assured.

# DOMESTIC PRODUCTION

# PRODUCTION OF PRIMARY AND REDISTILLED SECONDARY SLAB ZINC

The production of 891,872 short tons of primary slab zinc from domestic and foreign ores in 1942 was the highest ever made and exceeded the previous record of 1941 by 8 percent. This increase was made possible by a 55-percent larger output from foreign ore, which more than balanced the 3-percent decline in production from domestic ore.

Heavy demands on a dwindling supply of zinc scrap reduced the output of redistilled slab zinc in 1942 by 11 percent. To prevent inadvertent duplication, figures for the output of remelted secondary slab zinc are not included with those for redistilled metal. In 1942, 8,637 tons were recovered by remelting purchased scrap. Zinc rolling mills and other consumers recover considerably more than this from their own plant scrap, but such metal normally does not enter the market as scrap and is therefore not measured statistically.

Primary and redistilled secondary slab zinc produced in the United States, 1938-42, in short tons

		Primary		Total (ex- cludes zinc	
Year	Domestic	Foreign <sup>1</sup>	Total	Redistilled secondary	recovered by remelt- ing)
1938. 1939. 1940. 1941.	436, 007 491, 058 589, 988 652, 599 629, 957	10, 334 16, 178 85, 287 169, 421 261, 915	446,341 507,236 675,275 822,020 891,872	31, 613 50, 428 48, 917 59, 503 53, 195	477, 954 557, 664 724, 192 881, 523 945, 067

<sup>&</sup>lt;sup>1</sup> Most of the foreign ores smelted in the United States in 1938 originated in Peru; in 1938, in Mexico, Peru, and Argentina; in 1940–41, principally in Mexico, Canada, Newfoundland, and Peru; and in 1942, in Mexico, Canada, Argentina, Newfoundland, Australia, and Peru.

## DISTILLED AND ELECTROLYTIC ZINC

Of the primary zinc produced in 1942, 72 percent was distilled and 28 percent electrolytic compared with 73 and 27 percent in 1941.

The tremendous increase in the demand for wrought-brass products for military uses emphasized more than ever the importance of High-Grade slab zinc. In fact, it was found necessary to greatly enlarge the existing capacity to produce High-Grade zinc by redistilling Selected and Prime Western grades, the supply of which was not so critical. As a result the production of Special High Grade gained 14 percent and Regular High Grade 41 percent in contrast with Prime Western production, which was 21 percent lower. To avoid duplication the lower grades of zinc consumed in this operation

do not appear in the production figures shown in the following table, but the High-Grade slab zinc produced is included. Of the total 1942 production, 29 percent was Prime Western, 27 percent Regular High Grade, 24 percent Special High Grade, 9 percent Brass Special, 8 percent Intermediate, and 3 percent Selected.

Distilled and electrolytic zinc, primary and secondary, produced in the United States, 1938-42, in short tons

#### APPORTIONED ACCORDING TO METHOD OF REDUCTION

				Redistilled	secondary 1	
	Year	Electrolytic primary	Distilled primary	At primary smelters	At second- ary smelt- ers	Total
1938 1939 1940 1941 1942		93, 272 127, 056 187, 040 224, 313 252, 987	353, 069 380, 180 488, 235 597, 707 668, 885	14, 003 23, 471 20, 003 27, 904 20, 978	17, 610 26, 957 28, 914 31, 599 32, 217	477, 954 557, 664 724, 192 881, 523 945, 067

#### APPORTIONED ACCORDING TO GRADE

	Grad	de A		Grades	C and D			
Year	Special High Grade (99.99% Zn)	Ordinary	Grade B (Interme- diate)	Brass Special	Selected	Grade E (Prime Western)	Total	
1938 1939 1940 1941 1942		256 345 98, 940 177, 451 250, 501	58, 128 66, 591 65, 321 74, 797 77, 527		724 274 681 5, 152 26, 800	205, 846 242, 454 284, 131 347, 125 272, 641	477, 954 557, 664 724, 192 881, 523 945, 067	

<sup>&</sup>lt;sup>1</sup> For total production of secondary zinc see chapter on Secondary Metals—Nonferrous.

#### PRODUCTION OF PRIMARY SLAB ZINC BY STATES

Pennsylvania continued to be the leading producer of primary slab zinc in the United States—a distinction held without interruption since 1934. Montana ranked next followed closely by Illinois. Of the States for which production figures may be released, Oklahoma, Arkansas, and Idaho occupied the next three positions in order of decreasing importance. Arkansas and Oklahoma had less production than in 1941. Illinois was conspicuous with a 44-percent increase in 1942 output. Montana and Idaho, as usual, produced electrolytic zinc only. Illinois and Texas made both electrolytic and distilled metal, and all other producing States confined their operations to distillation alone.

Primary slab zinc produced in the United States, by States where smelted, 1938-42, in short tons

Year	Arkan-	Idaho Illinois	-	Mon- tana	Okla- homa	Pennsyl- vania	Other States 1	т	Total	
	S9S		Illinois					Short tons	Value	
1938 1939 1940 1941 1942	20, 476 19, 892 35, 497 44, 045 41, 649	15, 634 18, 427 37, 477 39, 285 39, 916	68, 167 79, 480 101, 819 121, 921 175, 455	77, 638 108, 629 149, 563 176, 406 193, 486	68, 224 84, 551 96, 689 105, 885 102, 422	139, 897 155, 598 175, 352 222, 486 231, 362	56, 305 40, 659 78, 878 111, 992 107, 582	446, 341 507, 236 675, 275 822, 020 891, 872	\$42, 849, 000 52, 753, 000 85, 085, 000 123, 303, 000 155, 186, 000	

<sup>&</sup>lt;sup>1</sup> Texas and West Virginia.

The second of th

#### SECONDARY ZINC

In addition to the redistilled secondary slab zinc (unalloyed) already reported herein, some remelted slab zinc is produced, and a large quantity of secondary zinc is recovered each year in the form of alloys, zinc dust, zinc pigments, and zinc salts. Additional information on secondary zinc is given in the chapter on Secondary Metals—Nonferrous.

# BYPRODUCT SULFURIC ACID

Sulfuric acid made from the sulfur dioxide gases produced in roasting zinc blende (sphalerite) is an important byproduct of zinc smelting. To utilize a larger proportion of their acid-producing capacity, some plants also consume large quantities of sulfur. The production of sulfuric acid at zinc-blende roasting plants increased 3 percent during 1942.

Sulfuric acid (60° B. basis) made at zinc-blende roasting plants in the United States, 1938-42

	Made from zine blende <sup>1</sup>		Made fro	m sulfur	Total 1		
Year						Valu	Le ²
	Short tons	Value <sup>2</sup>	Short tons	Value <sup>2</sup>	Short tons	Total	Average per ton
1938	466, 879 528, 872 586, 912 672, 177 695, 242	\$4, 253, 268 4, 765, 137 5, 364, 376 5, 706, 783 6, 570, 037	30, 996 102, 663 134, 250 148, 257 147, 513	\$282, 373 924, 993 1, 227, 045 1, 258, 702 1, 393, 998	497, 875 631, 535 721, 162 820, 434 842, 755	\$4, 535, 641 5, 690, 130 6, 591, 421 6, 965, 485 7, 964, 035	\$9. 11 9. 01 9. 14 8. 49 9. 45

<sup>1</sup> Includes acid from foreign blende.

# ZINC DUST

Production of zinc dust in 1942 was 7 percent below the record output in 1941. The zinc content of the dust ranged from 95 to 99.5 percent and averaged 97.2 percent. Of the total zinc dust shipped in 1942, 11 percent went to foreign countries. This percentage, based on data submitted to the Bureau of Mines, is probably low because sales to the Treasury Department are listed as domestic shipments, although the material eventually was shipped abroad to our Allies. Government restrictions curbing gold and silver mining resulted in a sharp decline in the use of zinc dust for precipitating these metals. Direct war uses, such as the use of dust in smoke screens and chemicalwarfare reagents, continued to increase. The largest single use for zinc dust was in the production of sodium hydrosulfite. Production and shipments during 1942 about balanced, so stocks at the end of the year were approximately the same as at the beginning. The average price of zinc dust shipped to domestic consumers in 1942 was 10.4 cents per pound as compared with an average of 9.3 cents in 1941. The raw materials used to manufacture dust are reviewed in the chapter on Secondary Metals-Nonferrous, since approximately 80 percent of it is produced from scrap items, principally galvanizers' dross. The balance is made from zinc ore, slab zinc, and as a byproduct of zinc refining.

<sup>2</sup> At average of sales of 60° acid.

# Zinc dust 1 produced in the United States, 1938-42

		Va	lue			Val	ue
Year	Short tons	Total	Average per pound	Year	Short tons	Total	Average per pound
1938	11, 609 16, 835 20, 731	\$1, 542, 511 2, 367, 861 3, 404, 970	\$0.066 .070 .082	1941 1942	24, 429 22, 805	\$4, 641, 580 4, 789, 050	\$0.095 .105

<sup>1</sup> All produced by distillation.

# ZINC PIGMENTS AND SALTS

The principal zinc pigments are zinc oxide and lithopone, and the principal salts are the chloride and sulfate. These products are manufactured from various zinciferous materials including ore, metal, scrap, and residues. Details of the production of zinc pigments and salts are given in the chapter on Lead and Zinc Pigments and Zinc Salts.

# MINE PRODUCTION

Mine production of zinc in the United States increased only 2.5 percent during 1942 to a total of 768,025 short tons of recoverable zinc. The Western States advanced 28,226 tons or 10 percent, the Central States declined 17,825 tons or 6 percent, and the Eastern States increased 8,499 tons or 4 percent. Oklahoma continued to be the principal producer in the country by a wide margin, contributing more than half of the yield from the Central States, which supplied 34 percent of the total mine production in 1942. The rapid depletion of ore reserves in the Central States lowered production in all but Wisconsin, Illinois, and Missouri. The Tri-State (Joplin) region supplied 31 percent of the total domestic production compared with 35 percent in 1941.

All Western States except Montana and Nevada gained in production during 1942 and together contributed 40 percent of the domestic total. Idaho continued to be the largest producer in this region, with a 10-percent increase over the previous record level of 1941. In spite of a drop in production, Montana ranked second, followed closely by New Mexico and Utah. The output of Colorado was more than double that of 1941. The 8-percent gain in Utah's output was due almost entirely to the additional production of the Tooele slag-fuming plant.

Among the Eastern States, New Jersey continued to be the leading producer and maintained its rank as second in importance in the country by mining 94,040 tons of recoverable zinc. The output from New York and Tennessee continued to be higher than in the past. Virginia mine production was somewhat smaller than in 1941.

Additional data on mine production of zinc are given in the separate chapters covering each State.

Mine production of recoverable zinc in the United States, 1925-29 (average) and 1938-42, by States, in short tons

State	1925-29 (average)	1938	1939	1940	1941	1942
Western States:						
Arizona	2,628	5, 814	6, 711	15, 456	16, 493	18, 522
California	3,999		6	79	440	613
Colorado	32,868	4, 553	1,830	5,060	15, 722	32, 215
Idaho	29, 128	44,030	47, 549	70,601	79,084	87, 256
Montana	72, 519	8,844	34, 799	52, 587	60, 710	54, 715
Nevada	5, 570	8,944	6, 228	11, 833	15, 129	10, 197
New Mexico	23, 351	28, 236	29, 356	30, 313	37, 862	46, 461
South Dakota						115
Utah	44, 385	33, 658	34, 526	43, 788	42,049	45, 543
Washington	575	11, 402	10, 131	11, 560	14, 320	14, 398
	215, 023	145, 481	171, 136	241, 277	281, 809*	310, 035
Central States:						
Arkansas	71	152	123	440	206	181
Illinois	1.174		334	4, 818	9, 198	9, 389
Kansas		73,024	68, 971	57, 032	71, 403	55, 874
Kentucky		322	909	1,278	427	407
Missouri	16, 708	10, 226	15,096	12,703	21, 932	36, 394
Oklahoma	226, 969	112, 924	140, 379	162, 935	166, 602	146, 510
Wisconsin	23, 055	2,073	5, 904	5, 770	6, 238	9, 426
	382, 944	198, 721	231, 716	244, 976	276, 006	258, 181
Eastern States:						
New Jersey	93, 839	85, 839	88, 716	91, 406	93. 781	94, 040
New York	7,091	29, 896	36,014	35, 686	38, 446	45, 807
Tennessee.		29, 810	32, 375	34, 796	36, 170	43, 971
Virginia		26, 956	23, 850	16, 927	22, 913	15, 991
	126, 753	172, 501	180, 955	178, 815	191, 310	199, 809
	724, 720	516, 703	583, 807	665, 068	749, 125	768, 025

Mine production of recoverable zinc in the United States, by districts that produced 1,000 tons or more during any year, 1938-42, in short tons

District	State	1938	1939	1940	1941	1942
Joplin region	Kansas, Southwestern Missouri, Oklahoma.	196, 174	224, 446	232, 437	258, 837	237, 936
New Jersey	New Jersey	85, 839	88, 716	91, 406	93, 781	94,040
Coeur d'Alene region	Idaho	31, 937	40,065	62, 948	68, 321	78, 313
St. Lawrence County	New York	29, 896	36, 014	35, 686	38, 446	45, 807
Eastern Tennessee	Tennessee	29, 810	32, 375	34, 796	36, 170	1 43, 971
Central	New Mexico	16, 695	23, 677	29, 573	34, 649	42, 374
Summit Valley (Butte)	Montana	942	20, 016	35, 899	38, 070	29, 313
Red Cliff	Colorado				10, 880	22, 880
Bingham	Utah Montana	23,096	20, 861	21,812	20, 496	22, 634
Smelter	Montana	6,063	12,639	14, 462	18, 751	20, 190
Austinville	Virginia	26, 956	23, 850	1 16, 927	122, 913	15, 793
Metaline	Washington	11, 402	10, 130	11,560	14, 201	13, 620
Park City region	Utah	1 5,678	9,054	17, 598	16, 177	13,026
Upper Mississippi Valley	Iowa, Northern Illinois, Wis- consin.	2,073	5, 904	5, 776	7, 956	11, 126
Pioche	Nevada	8,414	5, 737	10, 773	14, 391	8,957
Kentucky-Southern Illinois	Kentucky-Southern Illinois	322	1, 243	6,090	7, 907	8,096
Rush Valley	Utah	1.955	2, 370	2, 971	3, 726	7,625
Warm Springs	Idaho	12,070	7, 463	7, 104	8, 534	6, 260
Harshaw	Arizona		1,075	2,714	3, 531	4, 825
Pioneer	do	825	2,000	3, 175	4, 139	3,884
Leadville	Colorado	97	172	172	48	3, 344
Magdalena	New Mexico	218	317	206	2, 580	3, 185
Pioneer (Rico)	Colorado	30	867	2,607	3,008	2,764
Big Bug	Arizona		110	1,740	1,804	2,650
Wallapai	do	1,660	770	4, 295	2, 346	2, 244
Patagonia	do Utah		l	990	1,788	1,913
Tintic	Utah	921	851	225	797	1,708
South Mountain	Idaho	l		540	2, 201	1,485
Warren	Arizona		7	1,812	2,095	1,449
Heddleston	Montanadodo				548	1, 266
Montana	do		- 5	713	1,474	489
Animas	Colorado	1 132	574	1,394	832	379
Eagle	Montana	550	394	418	1,048	348
Ophir	Utah	1, 893	1, 268	603	173	189
Cataract	Montana	605	1,070	773	93	
Oro Blanco	Arizona	3, 265	2, 377	484		
Willow Creek	New Mexico	11, 291	4,925	l	l	

<sup>&</sup>lt;sup>1</sup> Includes very small quantity produced elsewhere in State.

# STOCKS

# PRODUCERS' STOCKS

Inventories at primary reduction plants at the end of 1942 were more than triple the amount on hand at the beginning, and the 241-percent increase raised the total to the highest point since 1939. Stocks held at secondary distilling plants, although comparatively small, advanced similarly from 890 to 1,790 tons to bring the over-all gain to 236 percent above 1941. Of the total stocks on hand at the end of the year, 18,058 tons were High Grade and Intermediate, and the remaining 66,364 tons were the lower grades, compared with 18,491 tons and 6,611 tons, respectively, at the end of 1941. Nearly the entire inventory gain can be accounted for by the accumulation of Prime Western grade.

This steadily increasing stock pile has been the outgrowth of the program of conservation, particularly with regard to nonessential uses, coupled with the necessity of building up reserves to a safe working level. Nearly half of the total stock on hand at the end of the year was credited to the account of the Metals Reserve Company. Although subject to allocation, a large proportion of the balance of Prime Western grade zinc probably will be refined into the higher-grade metal at some future date to help fulfill the demand for this critical material.

According to the American Zinc Institute, stocks of slab zinc followed a general downward trend until the end of May and then advanced rapidly during the remaining months of the year.

Stocks of zinc on hand at zinc-reduction plants in the United States at end of year, 1938-42, in short tons

	1938	1939	1940	1941	1942
At primary reduction plantsAt secondary distilling plants	157, 511 1, 915	83, 728 2, 555	19, 212 761	24, 212 890	82, 632 1, 790
	159, 426	86, 283	19, 973	25, 102	84, 422

Stocks of zinc ore (60 percent concentrates) in the Tri-State district (as reported by the Tri-State Zinc and Lead Ore Producers' Association) on January 3, 1942, were only 1,500 tons but quickly attained the level of 4,970 tons by January 24. Production continued to exceed shipments until the middle of February, when stocks were 5,805 tons. This rise was followed by a slow drop to 3,331 tons on hand at the end of the first quarter. The premium-price plan covering overquota mine production subsequently disturbed normal stock trends by encouraging the practice of making heavy shipments at the end of the month, with a resultant sharp drop in stocks. Throughout April, May, June, and July inventories remained fairly steady near 3,800 tons. August saw an accumulation up to 4,600 tons, but during September, October, and November stocks returned to the general level of 3,800 tons. By the middle of December the total reached 5,116 tons,but heavy shipments resulted in a January 2 inventory of only 957 tons.

According to an American Zinc Institute survey, stocks of ore and concentrates at primary zinc reduction plants on December 31, 1942,

191 ZINC

The second of th

totaled 540,339 tons averaging 55 percent zinc compared with 413,427 tons containing 55 percent zinc at the end of 1941. Smaller stocks of ore were also held at plants producing zinc oxide and zinc dust.

Data on stocks of metallic zinc outside the United States continue to be unavailable, owing to the disruption of international trade in zinc ore and strict censorship imposed by the Nations at war.

#### CONSUMERS' STOCKS

Consumers of slab zinc improved their inventory position in 1942, total stocks on December 31 being 6 percent above the amount on hand on the corresponding date at the end of 1941. Stocks increased steadily from the beginning of the year until August 31, when the maximum of 84,900 tons was attained. This was followed by a drop to 64,800 tons on November 30, the low point for the year. Galvanizers decreased their inventories by 23 percent during the year, but stocks at brass mills rose 57 percent. Because of variance in coverage and certain changes in industrial classification all stock figures for December 31, 1941, which appeared in the 1941 chapter were revised. At the average monthly rate of consumption in 1942 stocks on hand at the end of 1942 were sufficient to supply consumers' requirements for slightly more than 1 month.

In addition to physical stocks on hand at consumers' plants at the end of 1942, a total of nearly 21,000 tons of zinc was in transit to consumers, held for redistillation, and in dealers' hands. Exclusive of an indeterminate amount in bonded warehouses the approximate total slab zinc in stock (including inventories at producers' plants) on December 31, 1942, amounted to 176,000 tons. The comparative

figure at the end of 1941 was 106,000 tons.

Consumers' stocks of slab zinc at plants at the beginning and end of 1942, by industries, in short tons

	Galva- nizers	Die casters 1	Brass mills 2	Zine rolling mills	Oxide plants	Others	Total
Dec. 31, 1941 <sup>3</sup>	33, 437	8, 295	20, 225	3, 373	317	1, 207	66, 854
	25, 729	9, 086	31, 713	3, 063	532	1, 074	71, 197

Includes producers of zinc-base die castings, zinc-alloy dies, and zinc-alloy rods.
 Includes brass mills, brass ingot makers, and brass foundries.
 Revised figures.

## DOMESTIC CONSUMPTION

# NEW SUPPLY

The following table shows the 5-year trend of primary slab zinc available for consumption in the United States. This calculated quantity, in effect, is equivalent to the slab zinc apparently made available each year for shipment to domestic consumers during the

In addition to primary zinc, 52,295 tons of redistilled secondary metal were made available to consumers in 1942 after allowance for

increased stocks at secondary smelters.

Primary slab zinc available for consumption in the United States, 1938-42, in short

	1938	1939	1940	1941	1942
Supply: Stock at smelters Jan. 1 Production Imports for consumption	79, 144 446, 341 7, 230	157, 511 507, 236 30, 960	83, 728 675, 275 1 16, 468	19, 212 822, 020 1 34, 554	24, 212 891, 872 1 36, 394
Total available	532, 715	695, 707	775, 471	875, 786	952, 478
Withdrawn: Exports Stock at smelters Dec. 31	<sup>3</sup> 200 157, 511	4, 515 83, 728	79, 091 19, 212	89, 309 24, 212	133, 981 82, 632
Total withdrawn	157, 711	88, 243	98, 303	113, 521	216, 613
Available for consumption	375, 004	607, 464	677, 168	762, 265	735, 865

## CONSUMPTION

Approximately 600 companies, representing better than 95 percent of the consuming industry in the United States, used 728,169 tons of slab zinc in 1942—a 12-percent drop from the 1941 total of 827,435 tons. Receipts reported for this same period were 732,512 tons. parent discrepancy between this figure and the calculated 788,160 tons of primary and secondary slab zinc apparently shipped to domestic consumers in 1942 may be attributed largely to variances in metal in transit, unaccounted-for metal stored in bonded warehouses, and incomplete coverage of the survey.

Industrial mobilization for total war made startling changes in 1942 in the various phases of the zinc-consuming industry under close Government control. In comparison with 1941, zinc consumed in galvanizing dropped 29 percent and in brass products gained 40 per-The manufacture of zinc-base alloy was cut more than half, as was the use of slab zinc in zinc oxide, and rolled zinc decreased 8 Details are shown in the following table. percent.

Consumption of slab zinc in the United States, 1941-42, by industries, in short tons 1

	1941	1942		1941	1942
Galvanizing: 2 Sheets	129,028	76, 106	Zinc oxide	16, 128	7, 977
Tubes and pipe Wire Wire cloth Shapes 4	69, 749 41, 408 11, 307 99, 362	47, 085 35, 216 7, 320	Zinc-base alloy: Die castingsAlloy dies and rod	(3) (3)	58, 918 21, 227
Snapes *	350, 854	247, 491	Other uses:	150,853	80, 145
Brass products: Sheets, tubes, etc Ingots, castings, etc	195, 714 32, 324	292, 820 27, 126	Slush castings	751 1, 767 1, 431 5, 564	552 1, 667 1, 251 3, 095
Rolled zinc	228, 038 72, 049	319, 946 66, 045	wiscenaneous •	9, 513	6, 565
Itorieu zinc	12,010	00,040	Total: All uses	827, 435	728, 169

Based upon canvass of approximately 600 companies.

<sup>&</sup>lt;sup>1</sup> General imports.
<sup>2</sup> Not separately recorded; estimated.

Includes zinc used in electrogalvanizing but excludes sherardizing.
 Separate figures for 1941 not available.

<sup>4</sup> Includes pole-line hardware, hollow ware, chains, and miscellaneous articles not elsewhere mentioned.
4 Includes zinc used in manufacture of zinc dust, bronze powder, alloys, chemicals, castings, and miscellaneous uses not elsewhere mentioned.

zinc 193

The consumption of zinc in sheet galvanizing fell off 41 percent, and the amount used for this purpose was 31 percent of the total consumed in all galvanizing compared with 37 percent in 1941. In contrast, zinc used in coating shapes (largely items for military and naval use), although 18 percent under the 1941 figure, comprised 33 percent of the total as against 28 percent in the previous year. The balance of the zinc used in galvanizing went into tubes and pipe, wire, and wire cloth, all totals being less than in 1941.

Of the total slab zinc consumed in 1942, brass mills, foundries, and ingot makers absorbed 44 percent compared with 28 percent in 1941. The marked gain in zinc used for sheets and tubes, amounting to 50 percent, shows the urgent need for brass in cartridges and shell cases. The successful use of steel for certain of these items did not lessen the need for brass; rather it augmented a supply that otherwise would

have been limited by the availability of zinc and copper.

The vastly increased use of High-Grade slab zinc by the brass mills left a much smaller proportion available to the producers of zinc-base alloys. Moreover, rigid military specifications prohibited the use of zinc-base die castings in much of the war equipment. As a direct result of the aircraft expansion program, greater quantities of zinc-base alloys were needed for making stamping and forming dies used in fabricating certain airplane parts. Despite the marked gain of this specific type of use, over-all consumption of slab zinc in zinc-base alloy decreased 47 percent.

Zinc rolling mills showed only an 8-percent drop in slab-zinc consumption. In addition to slab zinc, the rolling mills remelt and reroll the metallic scrap originating during their fabricating operations. The scrap thus treated in 1942 amounted to 15,641 tons—a 7-percent gain over 1941. In addition, 2,023 tons of purchased zinc scrap in the form of zinc clippings, old zinc scrap, and engravers' plates were melted and rolled in 1942. No comparative data for 1941 are available. The zinc lost in such waste products as skimmings and ashes totaled 1,639 tons in 1942, an amount equivalent to about 2.4 percent

of the net production of rolled zinc.

Production of rolled zinc from these raw materials amounted to 66,439 tons—a 6-percent decrease from 1941. The average value advanced 6 percent from \$0.115 in 1941 to \$0.122 in 1942. Inventories of rolled zinc were 1,619 tons on December 31, 1942, as compared with 1,300 tons for the same date in 1941—an increase of 25 percent. In addition to actual shipments of rolled zinc in 1942 amounting to 43,647 tons, the rolling mills consumed 38,104 tons of rolled zinc in the manufacture of 22,463 tons of fabricated products, such as battery cans.

Rolled zinc produced and quantity available for consumption in the United States, 1941-42

		1941			1942	
		Valu	e		Val	ue
	Short tons	Total	Average per pound	Short tons	Total	Average per pound
Production: Sheet zinc not over 0.1 inch thick Boiler plate and sheets over 0.1 inch thick Strip and ribbon zinc 1 Foil, rod, and wire 2	18, 823 3, 610 47, 046 1, 084	\$4, 933, 000 775, 000 10, 125, 000 391, 000	\$0.131 .107 .108 .180	14, 554 3, 542 46, 930 1, 413	\$4, 191, 000 790, 000 10, 610, 000 564, 000	\$0. 144 . 112 . 113 . 200
Total rolled zinc	<sup>3</sup> 70, 563	<sup>3</sup> 16, 224, 000	3.115	66, 439	16, 155, 000	. 122
Imports Exports Available for consumption	271 4, 670 66, 164	54, 500 1, 141, 800	.100	50 3, 880 4 62, 280	10, 100 1, 013, 500	. 101 . 131
Value of slab zinc (all grades) Value added by rolling			.075 3.040			. 087 . 035

<sup>1</sup> Figures represent net production. In addition, 14,586 tons of strip and ribbon zinc in 1941 and 15,641 tons in 1942 were rerolled from scrap originating in fabricating plants operated in connection with zinc rolling mills.

Potts on foll, rod, and wire shown for the first time. Statistics for prior years excluded to prevent revealing individual company figures.
 Total figures for 1941 are higher than previously published owing to the addition of foll, rod, and wire.
 Allowances made for change in producers' stocks of rolled zinc; stock data obtained for first time in 1942.

The use of slab zinc for zinc oxide was cut to practically half that of 1941. Slab zinc is used to make French process oxide which represented approximately 16 percent of the total oxide made in 1942. the total French process oxide produced, about 58 percent was made

from slab zinc and the remainder from scrap.

Zinc slab differs from most metals in that it is refined into six grades of purity, ranging from Special High Grade containing 99.99 percent zinc to Prime Western grades containing less than 98.75 per-The following table shows the grades of zinc consumed by the various industries in 1942. Of the 700,731 tons of domestic slab zinc consumed, 33 percent was Prime Western, 28 percent Special High Grade, and 25 percent Regular High Grade. Nearly 83 percent of the total slab zinc used by galvanizers was Prime Western Grade in 1942; the high grades of zinc, principally in the form of anodes, were used for the most part by the electrogalvanizers. As die castings require the highest-purity metal, consumption by their producers is limited almost entirely to High-Grade slab zinc. War demands for lead-free wrought brass products, such as cartridge cases, were responsible for 84 percent of the slab zinc used by the brass-mill group being of the three highest grades. Zinc rolling mills consume very little slab zinc below the grade of Brass Special.

The Carles of the Contract of

CONTRACTOR OF THE PROPERTY OF

Consumption of slab zinc in the United States, 1941-42, by grades according to industry, in short tons

	Special High Grade	Regular High Grade	Inter- mediate	Brass Special	Selected	Prime Western	Foreign	Total
1941: Galvanizers	16, 375	8, 406	20, 147	1,746	177	296, 992	7, 011	350, 854
Die casters	145, 744	3, 324	618	2	1	270	894	150, 853
Brass mills	42, 829	85, 974	34,822	13, 678	5, 094	19,801	25, 840	228, 038
Zinz rolling mills Zinc oxide	1, 550 1, 169	22, 597 14, 359	13, 151	20, 676	8, 325	2, 607	3, 143 600	72, 049 16, 128
Other	4, 261	2, 031	512	- 51	6	1,728	924	9, 513
Total	211, 928	136, 691	69, 250	36, 153	13, 603	321, 398	38, 412	827, 435
1942:								
Galvanizers	7, 272	9, 189	11, 599	4, 452	831	204, 622	9, 526	247, 491
Die casters 1	78, 227	1, 913	5			01 210	15.157	80, 145
Brass mills 2	103, 003	134, 465	30, 152	10, 523	5, 334 35	21, 312 3, 173	2, 347	319, 946 66, 045
Zinc rolling mills	2, 197 1, 579	19, 708 6, 117	11, 108	27, 477	80	281	2, 347	7, 977
Zinc oxide Other	1, 405	1, 897	889	138	51	1,777	408	6, 565
Total	193, 683	173, 289	53, 753	42, 590	6, 251	231, 165	27, 438	728, 169

Includes producers of zinc-base die castings, zinc-alloy dies, and zinc-alloy rods.
 Includes brass mills, brass ingot makers, and brass foundries.

## PRICES

The informal base price ceiling of 8.25 cents a pound for Prime Western at St. Louis, established by the Office of Price Administration on October 9, 1941, was replaced by Price Schedule 81, effective January 29, 1942. As a result, control became stricter, but the quotations remained unchanged. The following formal ceilings were established per pound f. o. b. East St. Louis: Prime Western grade, 8.25 cents; Selected, 8.35 cents; Brass Special, 8.50 cents; and Intermediate, 8.75 cents. Regular High-Grade and Special High-Grade price ceilings were set at 9.25 cents delivered. The base price of 60-percent zinc concentrates in the Joplin region remained stationary at \$55.28 per ton. In comparison with 1942 prices, which remained unchanged throughout the year, the average price for Prime Western zinc in 1941 was 7.48 cents a pound and 60-percent concentrates at Joplin, \$49.80 a ton. The premium price plan is briefly outlined in this chapter under the heading, War-Agency Regulations.

The official British price of £25 15s. for foreign zinc delivered con-

sumers, duty paid, and £26 10s. for domestic metal remained unchanged throughout 1942.

Price of zinc and zinc concentrates, 1938-42

		,	-			
		1938	1939	1940	1941	1942
Average price of common zinc at—	_			0.04	<b>F</b> 40	. 05
St. Louis (spot)		4. 61	5.12	6. 34	7. 48 7. 87	8. 25 8. 66
New York	do	4.99	5. 51	6.73		
London		3.05	1 2.89	(2)	(2) (4)	(3) (4)
Excess New York over London	do	1.94	8 2. 03	(4)	(*)	(*)
Joplin 60-percent zinc concentrates:	· 1	-				
Price per short ton	dollars	27.83	34.15	41.87	49.80	55. 28
Price of zinc content	cents per pound	2. 32	2.85	3.49	4.15	4. 61
Smelter margin	do	2. 29	2. 27	2.85	3. 33	3.64
Price indexes (1925-29 average=100):						
Zinc (New York)		70	77	95	111	122
Lead (New York)		63	68	69	78	87
Copper (New York)		70	75	77	80	80
		74	79	82	85	87
All commodities 5		80	79	80	89	101
Wil commodifies			<del></del>			

Average for 8 months; London Metal Exchange dealings suspended in September.
 Official maximum price fixed by British Ministry of supply at £25 15s., equivalent to 4.64 cents a pound at the official 1941-42 rate of exchange.
 Difference based upon 8-month averages.
 Not available.
 Based upon price indexes of U. S. Department of Labor.

Average monthly quoted prices of common zinc (prompt delivery or spot) at St. Louis and London, and of 60-percent zinc concentrates at Joplin, 1941-42 1

		1941			1942	
Month	60-percent zinc concen- trates in the		ound)	60-percent zinc concen- trates in the		zine (cents ound)
	Joplin region (dollars per ton)	St. Louis	London	Joplin region (dollars per ton)	St. Louis	London
January February March April May June July August September October November December	\$48. 20 48. 22 48. 19 48. 20 48. 21 48. 21 48. 21 48. 22 48. 39 52. 88 55. 28	7. 25 7. 25 8. 25	(2)	\$55. 28 55. 28	8. 25 8. 25	(2)
Average for year	49.80	7. 48	(2)	55. 28	8. 25	(2)

<sup>&</sup>lt;sup>1</sup> 1941 quotations from Metal Statistics, 1942; 1942 quotations from E&MJ Metal and Mineral Markets, 1942.

3 Official maximum price fixed by British Ministry of Supply at £25 15s., equivalent to 4.64 cents a pound at the official 1941-42 rate of exchange.

Average price received by producers for zinc, 1938-42, by grades, in cents per pound

	1938	1939	1940	1941	1942 2
Grade A.: 1 Special High Grade Regular High Grade Grade B: Intermediate	<b>5.03</b>	5. 34	6. 59	8.04 7.74 7.52	9.00 9.10 8.64
Grades C and D; 1	4.73 4.71 4.8 4.6	5. 00 5. 08 5. 2 5. 1	6. 04 6. 14 6. 3 6. 3	7.37 6.64 7.16 7.5 7.5	8. 32 8. 18 8. 23 8. 7 8. 25

<sup>1</sup> American Metal Market quotes average prices of High Grade and Brass Special as follows: High Grade (f. o. b. New York)—1938, 5.74 cents; 1939, 6.16 cents; 1940, 7.38 cents; 1941, 8.48 cents; 1942, 9.25 cents. Brass Special (f. o. b. East St. Louis)—1938, 4.71 cents; 1939, 5.22 cents; 1940, 6.44 cents; 1941, 7.68 cents; 1942, 8.50 cents.

## Does not include overquota premium payments made by Metals Reserve Co.

# ZINC-REDUCTION PLANTS

#### ZINC SMELTERS

No change took place during 1942 in the number of zinc smelters. As in 1941, there were 17 active plants, of which 13 continued to operate with horizontal retorts exclusively, one with both horizontal and vertical retorts, two with large vertical retorts, and one with electrothermic furnaces. The total number of retorts reported at the horizontal-retort primary plants was 67,816, 2 percent less than the 69,552 (revised figure) at these plants on December 31, 1941. Of the total retorts reported, 65,508 were in use at the end of 1942—a minor decrease from the 65,969 in operation at the close of 1941. The increased output in 1942 from a numerically smaller number of retorts was accomplished by the use of larger retorts and increased efficiency of operation. Although only 97 percent of the available retorts was in operation at the end of the year, smelting operations

ZINC 197

THE THE SAME AND AND ASSESSED TO SAME AND AND AND ASSESSED ASSESSED ASSESSED.

were at usable capacity throughout 1942; the remainder, for the most part, comprised a decreasing amount of obsolete equipment that has been idle for some time and is being replaced or reconditioned, and a certain percentage that must necessarily be closed down for repairs and replacement. At the end of 1942, 4,896 new retorts were under construction. Of the 66 vertical retorts in this country, 63

were in operation at the year's end.

Twelve of the primary smelters mix scrap and residues such as skimmings and dross with the ore before distillation. Small quantities of clean metallic scrap are occasionally added to the (condensed or molten) primary zinc without affecting the quality. Supplementing these 17 primary producers, 15 plants made redistilled secondary slab zinc by treating scrap in 2,560 clay retorts, 112 graphite crucibles, and a few special furnaces. One plant at Philadelphia plans to add 3 graphite crucibles in 1943. A part of this available production capacity at secondary smelters is used to produce zinc dust and zinc oxide in addition to slab zinc.

# ELECTROLYTIC PLANTS

Five electrolytic plants were in operation by the end of 1942 compared with four in 1941. The American Smelting & Refining Co. started producing slab zinc in its new plant at Corpus Christi, Tex., during October and by December was operating at about 94 percent of capacity. Lack of raw materials delayed completion of additional new cells at the East St. Louis electrolytic refinery. By the end of 1942, 2,814 cells out of a total of 3,038 were in use compared with 2,502 out of 2,526 cells in 1941. The seemingly large number of unused cells is probably due to the fact that some were not completed. At the end of 1942, 156 cells were under construction in the country.

# FOREIGN TRADE 3

#### IMPORTS

The following tables give total zinc imports (general) in ore and blocks, pigs, or slabs into the United States, 1940–42, and imports for consumption. Of the 368,355 tons of zinc imported in ore, 44 percent came from Mexico, 21 percent from Canada, and 9 percent from Australia. Receipts from Canada were 58 percent higher and from Australia almost four times larger than in 1941. Imports from Belgian Congo dropped considerably, but all other countries supplied more ore than in 1941. Imports of slab zinc from Mexico increased 33 percent, whereas receipts of slab zinc from Canada declined 67 percent.

<sup>&</sup>lt;sup>3</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Zinc imported into the United States in ore, blocks, pigs, or slabs, 1940-42, by countries, in short tons 1

Country	1940	1941	1942
Ore (zinc content):     Argentina.     Australia     Belgian Congo     Bolivia.     Canada.     Chile.     Mexico.     Newfoundland and Labrador     Peru     Spain.	6, 723 1, 749 2, 530 33, 993 611 93, 789 23, 640 17, 285	20, 579 8, 933 12, 563 2, 687 49, 764 2, 157 148, 201 7, 267 28, 833	23, 395 32, 212 2, 873 5, 893 78, 744 6, 872 160, 713 30, 103 27, 506
Other countries		8, 227	44
	180, 320	289, 213	368, 355
Blocks, pigs, or slabs:  Belgium Canada Indochina, French Mexico	336 6, 938	7, 236 1, 653	2, 392
MexicoOther countries	8, 948 246	25, 621 44	34,002
그리고 함께 반면 하는 그 이 하는 것 같아. 아니다	16, 468	34, 554	36, 394

<sup>1</sup> Data include ore imported for immediate consumption plus material entering country under bond.

# Zinc imported for consumption in the United States, 1938-42, by classes

Year		Ores (zinc con- tent)		Blocks, pigs, or slabs		ieets	Old, dross, and skimmings <sup>1</sup>		Zine dust		Total
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	value 3
1938 1939 1940 1941 1942	4, 860 33, 503 44, 637 154, 520 268, 470	\$392, 591 1, 304, 433 1, 108, 361 4, 596, 480 10,460,541	7, 230 30, 960 10, 146 40, 288 36, 395	\$480, 169 1, 890, 236 801, 331 3, 661, 549 2, 927, 079	226 178 18 271 50	\$25, 989 21, 166 2, 796 54, 464 10, 086	96 203 520 456 3,342	\$8, 944 14, 067 36, 689 31, 695 156, 288	64 41 140 702	\$5,074 3,388 21,495 43,464	\$912, 76' 3, 233, 290 1, 949, 17' 8, 365, 68' 13, 537, 450

Includes dross and skimmings as follows—1939: 30 tons, valued at \$1,918; 1940: 356 tons, \$21,815; 1941:
 353 tons, \$23,028; and 1942: 3,199 tons, \$148,272. None reported in 1938.
 In addition, manufactures of zinc imported as follows—1938: \$463; 1939: \$1,545; 1940: \$32; 1941: \$1,099; 1942: \$16.

#### **EXPORTS**

The value of exports of zinc ore and manufactured articles containing zinc of foreign and domestic origin (excluding galvanized products, alloys, and pigments) amounted to \$24,551,255 in 1942 compared with \$14,717,513 in 1941. Slabs, plates, or blocks continued to be the largest export group, and the total shipped to foreign countries increased 50 percent—from 89,309 tons in 1941 to 133,981 tons in In addition to the items shown in the accompanying tables, considerable zinc is exported each year in brass, pigments, chemicals, and galvanized iron and steel. Export data on zinc pigments and chemicals are given in this volume in the chapter on Lead and Zinc Pigments and Zinc Salts. Much of the zinc used in the manufacture of such products is of foreign origin, and when they are exported a draw-back of 99 percent of the import duty is paid on the basis of zinc contained in the finished product. For 1942, draw-back was paid on 23,047 tons of zinc, of which 8,677 tons had been imported as slabs and 13,580 tons as ore. Totals for preceding years were: 1941, 34,478 tons; 1940, 19,306 tons; 1939, 16,213 tons; 1938, 11,550 tons; and 1937, 9,253 tons.

Slab and sheet zinc exported from the United States, 1939-42, by destinations, in short tons

Destination	Slat	Slabs, plates, and blocks				Sheets, strips, or other forms, n. e. s.			
	1939	1940	1941	1942	1939	1940	1941	1942	
Country:									
Argentina	56	890	862	<b>a</b>	404	579	504 464	1	
Australia					1,052 50	246 96	125		
Brazil	526 5	1, 391 (2)	1,004		2,902	2,813	1, 247		
Canada Chile	298	428	196	11	2, 502	130	144	1	
China	201	4, 115	1,947		148	40	102	il .	
France		8, 681	1,020	(1)	K			) (1)	
India and Dependencies		8, 68 <u>1</u> 9, 634	11, 553	1	122	1,422	672		
Japan	3, 252	13, 958	175		5	259			
Mexico			400	1			311		
U. S. S. R			480			585	209		
United Kingdom		36, 718	71, 325		841 1, 164	1, 320	1,468		
Other countries	177	3, 276	1, 367	<b>'</b>	\ 1,104	1, 520	1,400		
Total	4, 515	79, 091	89, 309	133, 981	6, 708	7, 490	5, 246	4, 76	
Continent:								100	
North America	31	258	433	,	( 3, 167	3, 127	1,721	1	
South America		2,760	2, 416	1	555	997	976		
South AmericaEurope		45, 982	71, 805	(1)	952	783	320	(1)	
Asia	3, 488	29, 431	14, 394	(b)	741	1,657	1, 431	()	
AfricaOceania		640	1		159	653	239		
Oceania	.	20	260	ĮJ .	1,134	273	559	J	

Data not available at time of publication.

2 Less than 1 ton.

Zinc ore and manufactures of zinc exported from the United States, 1938-42

Year	Zinc ore, concentrates, and dross (zinc content)		Slabs, plates, or blocks		Sheets, strips, or other forms, n. e. s.		Zine dust	
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
1938 1939 1940 1941	135 303 448	\$6, 404 11, 253 42, 207	(1) 4, 515 79, 091 89, 309 133, 981	(1) \$479, 338 9, 103, 030 12, 712, 121 22, 843, 391	1 5, 736 2 6, 708 2 7, 490 2 5, 246 2 4, 767	1 \$908, 381 2 1, 116, 485 2 1, 564, 720 2 1, 328, 516 2 1, 289, 889	2, 253 2, 384 3, 044 2, 901 1, 772	\$355, 856 468, 516 592, 271 676, 876 417, 957

<sup>&</sup>lt;sup>1</sup> Pigs and slabs not shown separately; included with sheets, strips, or other forms, n. e. s.

<sup>3</sup> Includes "Other forms, n. e. s. (including scrap)," as follows—1939: 259 tons, valued at \$64,434; 1940: 450 tons, \$13,652; 1941: 576 tons, \$186,731; and 1942: 887 tons, \$276,370.

<sup>3</sup> Less than 1 ton.

# WORLD ASPECTS OF ZINC INDUSTRY

The war continued to necessitate strict censorship regarding basemetal statistics from many countries. Although official zinc production figures were not, for the most part, available, some general information did filter through. The Bureau of Mines estimated that in 1942 the world mine production of zinc totaled about 2,044,000 short tons (recoverable zinc content) and that zinc smelter capacity amounted to approximately 2,950,000 tons. About 75 percent of the world supply of zinc ore and 54 percent of the total zinc smelting capacity is in the hands of, controlled by, or available to the United Nations. The inability of domestic supplies to pace a greatly expanded smelter capacity has aroused keen interest in all foreign deposits, of which the principal ones are discussed in the following pages.

World smelter production of zinc, 1937-42, by countries where smelted, in metric tons 1 [Compiled by B. B. Waldbauer]

Country	1937	1938	1939	1940	1941	1942
Australia	70, 869	70, 941	72, 363	<sup>2</sup> 85, 000	(3)	83, 316
Belgium 4	225, 580	210, 400	185, 700	2 65, 000	3	(3)
Canada	143,826	156,008	159, 338	168, 486	193, 784	195, 769
Czechoslovakia	7,336	8,876	(5)	(5)	(3)	(3)
France	60,427	60, 560	6ó, 262	2 35, 000	3	23
Germany 6	163, 814	194,370	7 212, 285	. (7 8)	(3)	(3) (3)
Indochina	4,204	4,470	5, 439	2 6, 700	(3)	94,647
T41	0='000	33, 637	33, 566	<sup>2</sup> 40, 000	\display \( \lambda \)	(3)
Japan Mexico	45,500	(8)	(8)	2 55, 000	2 65,000	(8)
Mexico	36, 587	35, 881	35, 369	33, 388	31, 543	X
Netherlands	24,645	25, 300	20, 500	<sup>2</sup> 6, 000	(3)	\ <u>\</u>
Northern Rhodesia	14, 256	10,379	12,899	15,000	}3√	
Norway		46, 523	45, 917	<sup>2</sup> 20,000	(3)	- 8
Poland	107, 174	108, 071	117, 936	<sup>2</sup> 120, 000	(3)	(3) (3)
Spain	1,843	7,672	13, 396	12,322	11, 589	10 3, 514
Union of Soviet Socialist Re-	-,0-0	.,	20,000	12, 022	11,000	1, 9, 914
publics	2 65, 000	(8)	(8)	(8)	(3)	(3)
United Kingdom 6	63, 138	56, 190	50,440	2 60, 000	(3)	(3)
United States		404, 912	460, 154	612, 596	745, 720	809, 088
Yugoslavia	4, 259	3,956	4, 182	6,025	(3)	(3)
	1, 623, 000	1, 568, 000	1, 635, 000	1, 643, 000	(3)	(3)

1 Statistical data derived in part from American Bureau of Metal Statistics, Yearbook.

**対対が 場合語が、** 

Estimated.
Data not available.
Includes the following tonnages of electrolytic zinc: 1937, 7,830 tons; 1938, 8,670 tons. Data not available for later years. Production of electrolytic zinc began in August 1935.
Included with Germany.
Some secondary metal included.
Includes Czechoslovakia.
Estimate included in total.
January to June, inclusive.
January to March, inclusive.

# REVIEW BY COUNTRIES

Argentina.—Practically all the zinc mined in Argentina is from the Aguilar mine of the St. Joseph Lead Co. in the Province of Jujuy, near the Bolivian border. Although no final data for 1942 are available, the reported monthly rate of production from this property alone. amounting to 6,000 to 6,500 metric tons of 54-percent concentrates, indicates that total Argentine output was above the 66,010 tons (36,300 tons zinc content) produced in 1941. Concentrates are transported to Santa Fé for shipment. Exports of this material in 1942 totaled 56,430 tons, all of which went to the United States. reported on hand at the mine in April totaled 115,000 tons; but by November 30, this stock, available for export, had been reduced to about 93,000 tons. An estimated 1,200 tons of concentrates a month, mostly from other smaller mines, is treated at the Puerto Vilelas smelter.

Australia.—The total production of zinc concentrates in Australia in 1942 was reported to be 387,000 long dry tons averaging about 53 percent zinc. No comparative data are available for 1941. In January 1943 the milling rate was 166,000 long tons of ore a month. war has hindered increased mining operations by necessitating higher taxation and the transfer of miners to the army and munition indus-Several expansion efforts have been delayed when construction lagged. Diamond drilling has been continued at New Broken Hill and has led to the location of a body of lead ore containing about 16 percent zinc. Production of zinc concentrates was maintained at the Mount Isa Mines, Ltd.

ZINC • 201

CHARLES THE SECOND STREET, STR

Operation of the smelter of the Electrolytic Zinc Co. at Risdon, Tasmania, was hindered by a labor shortage, and production failed to reach full capacity for a short time when an adequate supply of important operating reagent was not available. The Risdon plant produced about 82,000 tons of metal in 1942, but none was available to the United States.

Bolivia.—The mine production of zinc (content in ore) amounted to 10,909 metric tons in 1942 compared with 6,065 metric tons in 1941.

All production is exported.

The Huanchaca mine produces most Bolivian zinc by the cut-andfill method. Output has continued to be small, and no apparent

reserves are in sight.

Brazil.—The main deposits of zinc ore (blende) are in the Iporanga region of the State of São Paulo and the Morro do Bule and Januaria regions of the State of Minas Gerais. Reserves have been estimated at about 30,000 metric tons containing 31 to 36 percent zinc, but no

large deposits have been found.

Burma.—The fall of Lashio to the Japanese early in March 1942 precluded continued operation by the Burma Corporation of the mines at Bawdwin, and the properties were evacuated by April 25. Reportedly some damage was done to the mines, smelter, and equipment before evacuation, but the extent of destruction and its effect upon subsequent operations by the Japanese is not known. These mines had an annual production of about 45,000 long tons of zinc. The last available information on reserves at this mine (June 30, 1941) gives an estimate of 3,130,200 tons of ore assaying 15.1 ounces of silver,

19.5 percent lead, and 12.1 percent zinc.

Canada.—The war has brought considerable pressure on the Canadian mining industry to expand its output. As a result the 1942 mine output totaled 294,101 short tons (metallic content), an 11-percent gain over the 1941 production of 265,191 short tons. Because Canada has only two refineries—one at Trail and the other at Flin Flon—its ore production exceeds its refinery capacity. There has been considerable interest in building a zinc refinery in Quebec instead of sending the concentrates to the United States. As most of the excess concentrates are shipped to the United States, where the supply of raw material is critical, it is not surprising that the United States has been a guarantor for expansion of mills and other facilities to increase the output of zinc. Plans for a \$1,000,000 smelter to be built by the Reeves MacDonald mines south of Trail, British Columbia, and financed by United States funds have been under discussion, but nothing definite has yet materialized.

Of the total zinc mined in Canada, approximately 71 percent is produced in British Columbia (mostly from the Sullivan mine), 20 percent from Flin Flon, and 7 percent from the Noranda district. A large number of small, idle mines were reopened, and extensive diamond-drill prospecting was conducted. An important zinc deposit

was found near the Labrador border.

The Sherritt Gordon Mines, Ltd., located a new sulfide-ore deposit containing 1 percent copper and the same amount of zinc. A new zinc-concentrate plant is about completed, and the product will be purchased by the Metals Reserve Company with whom it has contracted to sell 50,000 tons of 50-percent zinc concentrates within a

2-vear period. Development work in the zinc deposit at Calumet Island was speeded up, owing to the demand for concentrates for smelters in the United States. The New Calumet expected to "tune up" its new 300-ton zinc-lead concentrator before the end of December. The Golden Manitou mine is constructing a 600-ton-a-day zinc concentrator. By October the Hudson Bay Mining & Smelting Co. had enlarged its plant to 6,200 tons daily capacity. A new shaft allows a higher metallic content ore to be drawn below the 2,250 level in the southern section. Zinc is recovered from a 300,000-ton residue pile averaging 23 percent zinc. Residues are treated with sodium chloride, and the zinc is roasted to yield zinc oxide. The company is selling its excess zinc to the United Kingdom at pre-war prices, with adjustments for increased costs. This same company has proved an important copper-zinc ore body at Schist Lake. Emergency Metals. Ltd., is equipping the Mandy mine with a 200-ton concentrating plant to treat an estimated 180,000 tons of ore averaging 20 to 38 percent zinc, 5 to 8 percent copper, and \$5 in gold and silver per ton. As of June 13, 1942, all imported zinc spelter and zinc in blocks. pigs, bars, or rods has been exempted from customs duty. According to the Department of Munitions and Supply, approximately 95 per-

cent of Canada's entire supply of zinc is devoted to essential and war uses, compared with 75 percent in 1941 and 36 percent in 1940.

Japan.—There are no known zinc deposits of commercial importance in Japan proper, but extensive ore bodies are reported in Chosen. Japan's estimated smelter output in 1941 was 65,000 metric tons. In April 1943 Japan captured the Bawdwin lead-zinc mines of the Burma Corporation, which are capable of supplying 45,000 (long) tons of zinc a year. During 1942 a trade agreement was made with French Indo-China in which Japan will help develop the zinc

deposits in that country.

Mexico.—Mine output of zinc in Mexico increased 22 percent from 154,996 metric tons (metal content) in 1941 to 189,278 metric tons in 1942. The most important event in 1942 was the Bateman-Juarez-Tellez agreement among the Metals Reserve Company, the State Department, and the Mexican Government, whereby the Metals Reserve Company contracted to buy 200,000 tons of zinc at 8.25 cents per pound each year for the duration of the war and extendible by mutual agreement after the war. Mexico agreed to stabilize taxes on zinc, freeze freight rates, and hold in abeyance certain clauses in the labor laws. In spite of this agreement labor difficulties appeared, and at the end of the year the miners were threatening to strike for a 25-percent wage increase. On December 23 a reciprocal trade pact between Mexico and the United States reduced the duty on slab zinc and zinc in ore to 50 percent of the amount set by the United States Tariff Act of 1930. The new rate places the tariff on slab zinc at \$0.875 cents a pound and zinc in ore and concentrates at \$0.750 cents.

The American Smelting & Refining Co. expanded its mining operations at Xichu, Tecolote, Taxco, and San Carlos. Old zinc mines in the Taxco district are being reopened by American Smelting & Refining Co. and Eagle Picher Lead Co. The Sociedad Cooperativa Minera "El Bote," S. C. L., at El Bote is treating 400 tons of lead-zinc Crude-ore production of five principal mines in the Chihuahua district increased in 1942 despite the fact that Potosi Mining Co. exhausted its main ore body after nearly 100 years operation. Nearly ZINC 203

all the cooperative mining companies reverted to private ownership and operation in 1942. It is reported that a large zinc deposit has been discovered in the Nacozari-Pilars district. The Moctezuma Copper Co. will treat the ore.

Inadequate transportation facilities have continually handicapped the movement of materials and are a limiting factor in further mine

expansion.

The Federal Power Commission granted permission to export Texas natural gas to the Rosita smelter of the American Smelting & Refining Co. It is expected that this move will boost zinc production at the only zinc smelter in Mexico an additional 2,400 to 4,800 tons per year.

North Africa.—The principal zinc deposits in North Africa are in the Province of Constantine, Algeria, where the ores—calamine, sphalerite, and galena—occur chiefly as replacement deposits in

limestone.

Deposits of ore are known in Tunisia north of Béja and Tunis, and south of Tunis is the Zaghouan concession containing calamine and lead ore. In this same vicinity at the Djebel Ressas concession zinc is mined in conjunction with lead. In the West lies the Sakiet-Sidi Youssef concession, south of Ghardimaou. It is reported that an electrolytic zinc plant was built in 1931 near Touireuf, but there is no record of its ever having operated. The output in Tunisia has fallen off considerably in recent years, largely owing to the depletion of known reserves.

The following table from Mineral Industries of North Africa, Special Supplement to Confidential Series 7, Mineral Trade Notes, lists the production, shipments, and stocks of zinc concentrates, in

metric tons, from January 1 to May 1, 1942.

	Production	Shipments	Stocks
Tunisia	840	368	1, 972 13, 091
Algeria Morocco	459 403	368 4, 300 800	13, 091 5, 511

Production of concentrates, available to the United Nations since the successful conclusion of the North African military campaign late in 1942 and the first months of 1943, is reportedly being shipped to the

United Kingdom for treatment.

Newfoundland.—In spite of a labor shortage that prevented capacity operations, 94,114 short tons of zinc concentrates averaging 53-percent zinc were produced in 1942. In addition 6,564 tons of zinc were recovered in lead and copper concentrates. The comparative figures for 1941 were 116,836 tons of 52-percent zinc concentrates and 8,745 tons of zinc recovered in lead and copper concentrates.

Norway.—Owing to the difficulty of obtaining raw materials, only 3,250 tons of zinc metal were produced from January to September 1942, as against 46,000 tons in the whole year of 1939. In addition

to Norwegian ore some Finnish and Swedish ore was used.

Northern Rhodesia.—At Broken Hill, Rhodesia, the Rhodesian Broken Hill Development Co., Ltd., operates the most important zinc mine in Africa. The ore contains 30 to 55 percent zinc plus lead and is associated with vanadium-bearing material.

Peru.—In 1942 the mines in this country produced 51,263 metric tons of 58-percent zinc concentrates, a substantial increase over the 1941 total of 40,800 tons containing 23,700 tons of extractable zinc. Zinc mining continued to be largely controlled by the Cerro de Pasco Copper Corporation which owns a zinc deposit in central Peru containing ore reserves estimated at 10,000,000 tons containing 17 percent zinc, 6 percent lead, and 6 ounces of silver per ton. The output from the Cerro de Pasco Casapalca mine, which decreased from 15,877 tons of concentrates in 1940 to 13,550 tons in 1941, probably was smaller This mine has a flotation plant with a daily capacity of 800 The Huaron mine of the Cie de Mines de Huaron is now producing at the rate of nearly 1,270 tons of 60-percent concentrates a month. In 1943 Cerro de Pasco should finish a new 800-ton daily capacity concentrator, under construction. The smelter at Oroya produces about 800 tons of refined zinc annually which is consumed in South America. Peruvian exports in 1942 were 247 metric tons of zinc in ore, 25,220 tons in concentrates, and 942 tons of refined zinc. Spain.—Three mines and one smelter were reported operating in Output of zinc concentrates in 1941 was estimated at 73,000 metric tons. The monthly production rate of zinc concentrates early in 1943 was between 5,500 and 6,000 tons, and the stocks on hand available for export were about 15,000 tons containing 58 percent zinc

and 7,000 tons containing 52 percent zinc. The Cie Royale Asturienne

des Mines enlarged its plant and installed a special furnace to produce high-grade zinc.

# LEAD AND ZINC PIGMENTS AND ZINC SALTS

By H. M. MEYER AND A. W. MITCHELL

#### SUMMARY OUTLINE

	Page		Page
General summary	208		
Salient statistics	207	Zinc oxide	212
Production	207	Leaded zinc oxide	
Lead pigments	208		
Zinc pigments and salts	209		213
Consumption by industries	210	Zine chloride	214
White lead	210	Zinc sulfate	214
Basic lead sulfate	210	Raw materials used in manufacture of lead and	
Red lead	210	zinc pigments and zinc salts	214
Orange mineral	21	Prices	216
Litharge		Foreign trade	217

## GENERAL SUMMARY

Activity in the pigments industry as a whole was sharply curtailed in 1942 from the rate that prevailed in 1941. This recession was due not to failure of demand but rather to restrictions in supplies of metal, scrap, and ores early in the year; to curtailment in the use of shipping drums, cans and other containers, brushes, drying oils, and other materials, as the year advanced; and also to conditions that revolutionized whole industries, such as the automobile industryone of the principal users of pigments. Another deterring factor was the regulation of the Office of Defense Transportation requiring that all shipments by rail be in full carlots or at least up to the full marked capacity of freight cars.

Supplies of zinc and lead metal were restricted throughout the year, but as increasing amounts of lead became available from a record rate of importation, limitations regarding its use were eased in November. Large-scale production of ilmenite began in New York in August, greatly changing the outlook concerning supplies of crude materials for the competitive titanium-pigment group. a result, restrictions on titanium pigments were lifted in December. The restrictions, nonetheless, had been responsible for what was probably the only noteworthy set-back thus far to the steady advance

of this group of pigments.

Consumption of the lead oxides for storage-battery manufacture in 1942 was considerably below the record quantities used in 1941, but except for that year it was higher than ever before. The amounts of zinc oxide and lithopone used in the manufacture of rubber dropped sharply. The outlook for future needs for this purpose is clouded by inability to gage requirements for the manufacture of synthetic The use of pigments in paints also fell sharply in 1942, except for red lead, which established a new high record. sulfate for paints and varnish processing was also consumed at a new high rate. Curtailment in the use of pigments by the ceramics industry was marked. On the other hand, agricultural use of zinc sulfate established a new high record in 1942.

According to the F. W. Dodge Corporation, new building construc-

tion in 1942 attained a new high record rate, exceeding the previous

The Lumber and Lumber Products Division record by 25 percent. of the War Production Board anticipates a noteworthy reduction in the number of board feet required by the Nation in 1943 as compared with 1942, or 31,100,000,000 compared with 40,300,000,000. peak of war construction at army cantonments, drydocks, airports, and shipyards obviously has passed. In 1942 paint materials were largely used to fill Government needs. In its January 11, 1943, issue the Oil, Paint and Drug Reporter estimated that by fall of 1942 the Government was taking approximately 60 percent of total paint materials compared with 25 percent in 1941 and 5 percent in 1940. large proportion of steel-construction paint requirements is indicated in part by the new high-record use of red lead in paint in 1942. This pigment is the only one in the group covered by this report that showed increased use for paint manufacture; it is well-known for its use in steel-construction paints.

During and after World War I the chemical industry in the United States made great progress. Dr. J. S. Long 1 says that the American paint industry will emerge from World War II independent of the importation of basic commodities from foreign countries. Many of the new products and processes developed since the start of the war have advantages over those used before that time.

The flexibility of the paint-mixing industry will be tested further by the recent (April 1943) amendment to War Production Board Order M-71 of the Fats and Oils Section of the Department of Agriculture, which reduced this trade's quota of linseed oil and of all other drying oils not required immediately for direct war effort and not already embraced in the edible and potential food categories from 60 to 50 percent of the average 1940-41 usage for the second quarter of 1943. Original Order M-71 (effective October 1942) cut chemical and vegetable oils to 70 percent. In a mimeographed release on conservation in the use of linseed oil in paint, Hickson 2 pointed out that linseed oil is the most widely used drying oil in the paint industry and that about 79 million gallons were consumed in 1940 and about 109 million in 1941, of which 75 to 80 percent was used in the paint and varnish industry. Consumption in 1942 was considered to have been higher than in 1940. Hickson said:

Nearly all the linseed oil used in the United States is manufactured there, but in 1940 more than one-third of the 31 million bushels of flaxseed required was imported, mainly from Argentina. Under present conditions practically no flax-seed is imported from South America. At the same time there have been new demands for the oil, in part to meet the needs of our Allies, and in part to replace other imported oils such as tung (China wood oil) and perilla oils that were used previously.

Adding to the list of paint components whose need as food material is considered greater than their desirability for paint and other industrial uses, the War Production Board has placed processed industrial casein under allocation control under Order M-307.

In connection with the container problems that developed during the year, an article by Lahey 3 probably will be of interest. Several papers on packaging problems were read at the 14th Annual Pack-

<sup>&</sup>lt;sup>1</sup> Long, J. S., War Jogs Us Out of Our Complacency: Paint Industry Magazine, vol. 58, No. 4, April 1943,

p. 138.

† Hickson, Eugene F., Conservation of Linseed Oil in Paint: Department of Commerce, Nat. Bureau of Standards Letter Circ. LC-717. February 10, 1943, 8 pp.

† Linkey, Richard W., Chemical Containers for the Duration: Chem. Ind., vol. 52, No. 3, March 1943, pp. 351-352.

aging Conference in New York early in April and were reviewed briefly

in the April 1943 issue of Chemical Industries (p. 482).

The increasing use of fiber drums, wood barrels, glass bottles, and wood boxes, as well as the exercise of great care in handling steel drums already in use in the industry, have tended to offset container difficulties.

Recently released data on the pigments industry in Canada in 1941 show that in that year the industry was at record levels there, as well as in the United States. The following statistics on the short tons used in manufacturing in 1941 (1940 in parentheses) should be of interest: White lead (dry) 2,164 (1,642), white lead in oil 714 (648), basic sulfate white lead 111 (64), litharge 729 (492), red lead 648 (597), zinc oxide (pure) 1,589 (1,680), zinc oxide (leaded) and zinc leads 2.255 (2.087), and lithopone 10,538 (8,194).

and zinc leads 2,255 (2,087), and lithopone 10,538 (8,194).

Through the Reciprocal Trade Agreement with Mexico, signed in December, the rate of duty on zinc oxide and on leaded zinc oxide containing not more than 25 percent of lead was reduced to 1½ cents a pound for oxide in dry form and 1½ cents a pound for that mixed with oil or water. The duty on zinc sulfate was cut to ½ cent a pound.

Salient statistics of the lead and zinc pigments industry of the United States, 1925–29 (average) and 1938–42

	1925–29 (average)	1938	1939	1940	1941	1942
Production (sales) of principal						
pigments:						
White lead (dry and in	11.11				440 000	
oil)short tons	154, 483	100, 213	98, 429	80, 562	113,000	83, 639
Lithargedo	84,845	68, 711	89, 518	89, 841	122, 280	91, 513
Red leaddo	41, 362	30, 183	39, 976	42, 200	53, 838	48, 369 99, 677
Zinc oxidedo	154, 208	79, 129	114, 552	113, 213	148, 833	
Leaded zinc oxidedo	26, 609	38, 216	42, 684	45, 362	68, 920	48, 128
Lithoponedo	177, 745	125, 746	142, 759	151,802	176, 642	137, 320
Welve of products						
Value of products: All lead pigments	\$60, 092, 000	\$28,351,000	\$35, 485, 000	\$32, 628, 000	\$46, 572, 000	\$39, 393, 000
All zinc pigments	41, 314, 000	23, 301, 000	28, 794, 000	28, 747, 000	39, 210, 000	30, 785, 000
An zinc pigments	11,011,000	20,002,000				
Total	101, 406, 000	51,652,000	64, 279, 000	61, 375, 000	85, 782, 000	70, 178, 000
Value per ton received by pro-						1.0
ducers:	100		1			100
White lead (dry)	178	123	138	137	147	160 150
Litharge	176	122	123	126	134	171
Red lead	193	137	140	141	161 125	138
Zinc oxide	133	117	117	118	118	129
Leaded zinc oxide	124	107	114	114	71	79
Lithopone	98	79	73	67	/1	19
Foreign trade:						
Lead pigments:						100
Value of exports	1, 346, 000	510,000	715,000	594,000	1, 228, 000	957, 000
Value of imports	30,000	10,000	10,000	14,000	12,000	4,000
Zinc pigments:	1				1	
Value of exports	2, 150, 000	339,000	925,000	1, 585, 000	3, 525, 000	2,740,000
Value of imports	931,000	285,000	280,000	46,000	22,000	8,000
Export balance	2, 535, 000	554,000	1, 350, 000	2, 119, 000	4, 719, 000	3, 685, 000

# PRODUCTION

In this report, sales are used as presenting a more accurate picture of the industry than production, partly owing to the lack of statistics covering inventories at the beginning and end of the year. One factor is that at times materials classified as one item for production have been sold later under another description. Thus, sales figures afford a more accurate measure of pigments as they go into consumption

channels. Moreover, pigments produced under one classification at a plant are sometimes employed at the plant of another company for blending into another product covered by the lead and zinc pigments canvass. To prevent duplication, the Bureau of Mines attempts to count the product only in the form in which it enters actual use. Basic lead sulfate used in the manufacture of leaded zinc oxide presents the principal problem in this connection. It is included in the statistics in this report at the leaded zinc oxide stage, at which point it enters use in paints. Some other blending is done; but it does not affect large amounts, and—insofar as possible—the duplication involved is eliminated. Production figures are employed in this report in calculating the metal content of pigments and salts in the section on Raw Materials Used in Manufacture of Lead and Zinc Pigments and Zinc Salts. Pigments used by producers in manufacturing products at their own plants are considered here as sales.

The total value of sales of lead and zinc pigments in 1942 was 18 percent below 1941, falling from \$85,782,000 to \$70,178,000. It was, however, higher than in the 11 years before 1941. The higher average prices generally received for the commodities covered by this report were responsible for the smaller drop in total value as compared with

that in the total quantity of the products.

Lead pigments.—In 1941 litharge, red lead, and white lead (dry) had reached new all-time peaks. The declines in these pigments, as well as in others in the lead group, in 1942 may be ascribed, in part at least, to artificial factors—those other than the actual demand. Under the influence of the heavy Government construction program red lead made the best showing of any pigment covered by this report; total sales fell only 10 percent compared with a 34-percent decline for dry white lead, the other extreme in activity among the important Sales of both red lead and litharge in 1942 exceeded those pigments. in all other years except 1941 and were 17 and 8 percent over the averages for 1925-29. White lead in oil decreased 18 percent from 1941, making a better showing than other lead pigments except red lead, but it continued below all others in its relation to other earlier years. Average values received by producers for all lead pigments showed gains in 1942 that ranged, except for the small-tonnage orange mineral, from \$9 a ton for white lead in oil to \$32 for blue lead sulfate. The lead-pigment group decreased 23 percent in total quantity and 15 percent in total value from 1941.

Lead pigments sold by domestic manufacturers in the United States, 1941-42

		1941		1942		
Pigment	Short tons			Short	Value (at plant, ex- clusive of container)	
	tons	Total	Average	tons	Total	Average
Basic lead sulfate or sublimed lead: White Blue Red lead Orange mineral Litharge White lead: Dry In oil 1	8, 739 1, 631 53, 838 246 122, 280 54, 689 58, 311	\$1, 122, 622 211, 816 8, 687, 469 57, 516 16, 416, 507 8, 013, 421 12, 062, 375	\$128 130 161 234 134 147 207	7, 229 1, 181 48, 369 128 91, 513 35, 865 47, 774	\$1, 107, 157 191, 811 8, 254, 230 30, 643 13, 756, 868 5, 743, 747 10, 308, 863	\$153 162 171 239 150 160 216

<sup>1</sup> Weight of white lead only but value of paste.

Lead pigments sold by domestic manufacturers in the United States, 1938-42, in short tons

Year	Whit	e lead	Basic lead sulfate or sublimed lead		Red lead	Orange	Litharge
	Dry	In oil	White	Blue		mineral	
1938. 1939. 1940. 1941. 1942.	29, 813 30, 509 30, 115 54, 689 35, 865	70, 400 67, 920 50, 447 58, 311 47, 774	5, 030 4, 688 5, 493 8, 739 7, 229	771 850 707 1, 631 1, 181	30, 183 39, 976 42, 200 53, 838 48, 369	127 131 137 246 128	68, 711 89, 518 89, 841 122, 280 91, 513

Zinc pigments and salts.—In the zinc-pigment group leaded zinc oxide established a new high record in 1941. It dropped 30 percent in 1942 but remained above all previous years except 1941. This pigment has been increasingly popular in recent years, and another factor that permitted a better than average record in 1942 was that it was made almost entirely from ores, supplies of which were not as short as of either metal or scrap (other sources of zinc in pigments). Zinc oxide (lead-free) sales were down 33 percent from 1941. Stringent supplies of zinc metal and scrap have had a marked effect on the production of this pigment. Sales of lithopone also were lower than in 1941, having fallen 22 percent. Altogether zinc pigments decreased 28 percent in total quantity in 1942, but they dropped only 21 percent in total value because producers of all types received higher per-ton average prices.

Zinc pigments and salts sold by domestic manufacturers in the United States, 1941-42

		1941			1942	
Pigment or salt	Short tons	Value (at clusive of c	plant, ex- container)	Short	Value (at clusive of	plant, ex- container)
	tons	Total	Average		Total	Average
Zine oxide ¹ Leaded zine oxide ¹ Lithopone Zine chloride, 50° B Zine sulfate	148, 833 68, 920 176, 642 (2) 19, 201	\$18, 558, 474 8, 101, 782 12, 550, 193 (2) 1, 424, 456	\$125 118 71 (²) 74	99, 677 48, 128 137, 320 52, 374 14, 331	\$13, 746, 599 6, 209, 558 10, 828, 924 2, 789, 430 1, 179, 281	\$138 129 79 53 82

<sup>&</sup>lt;sup>1</sup> Zinc oxide containing 5 percent or more lead is classed as leaded zinc oxide.

Data not available.

Zinc pigments and salts sold by domestic manufacturers in the United States, 1938-42, in short tons

Year	Zinc oxide	Leaded zinc oxide	Lithopone	Zinc chlo- ride (50° B.)	Zinc sulfate
1938. 1939. 1940. 1941.	79, 129 114, 552 113, 213 148, 833 99, 677	38, 216 42, 684 45, 362 68, 920 48, 128	125, 746 142, 759 151, 802 176, 642 137, 320	(1) (1) (1) (1) (1) 52, 374	7, 757 10, 157 11, 937 19, 201 14, 331

<sup>1</sup> Data not available.

Sales of zinc chloride totaled 52,374 tons (50° B.) in 1942. Comparable data for a number of earlier years are not available. The figures for 1942 include the equivalent zinc chloride content of chromated zinc chloride and zinc ammonium chloride sold.

Except for the high record quantity for 1941, sales of zinc sulfate were at peak levels in 1942. The total for 1942 lagged 25 percent behind 1941 which, however, was 61 percent above the previous record,

attained in 1940.

### CONSUMPTION BY INDUSTRIES

White lead.—Sales of dry white lead declined 34 percent from 1941, and the "in oil" variety fell 18 percent; the total was 26 percent below 1941 and 46 percent less than the 1925–29 average. The predominant use of both classes of product is in the manufacture of paints, and 92 percent was so used in 1942.

Distribution of white lead (dry and in oil) sales, 1938-42, by industries, in short tons

	Industry	1938	1939	1940	1941	1942
PaintCeramics		 95, 018 1, 918 3, 277	92, 380 1, 767 4, 282	73, 137 3, 029 4, 396	100, 665 3, 704 8, 631	76, 837 1, 812 4, 990
		100, 213	98, 429	80, 562	113, 000	83, 639

Basic lead sulfate.—Basic lead sulfate also goes mainly into paints, either directly or as a component of leaded zinc oxide. The statistics for basic lead sulfate do not include the quantity used for blending into leaded zinc oxide, the amount so used being accounted for under the latter pigment. In 1941 the use of basic sulfate in the manufacture of leaded zinc oxide reached a peak total of 12,000 tons; in 1942 it amounted to 6,000 tons.

Distribution of basic lead sulfate sales, 1938-42, by industries, in short tons

Industry	1938	1939	1940	1941	1942
PaintsRubber	5, 024 91 3 683	5, 170 140 4 224	5, 593 128 4 475	9, 285 200 8 877	7,733 89 588
	5, 801	5, 538	6, 200	10, 370	8, 410

Red lead.—This pigment receded from its peak performance in 1941 but maintained a high rate of activity in the face of more serious declines all along the line. Sales in 1942 were 10 percent below 1941 but, except for that year, were the highest ever recorded, surpassing even the heavy construction period in the prosperous twenties. An important reason for the favorable record is the performance of this pigment in construction paints. Red lead is used principally in the manufacture of storage batteries. Its use for this purpose was below the amounts so consumed in 1939, 1940, and 1941, whereas sales for paint manufacture were at new high record levels in 1942. In 1939–40 paint manufacture took 28 percent of the total red lead sold, whereas in 1941 and 1942 it took 37 and 43 percent.

Distant hards are of ward	1	1000 10	7	
I FISHTIULLIUM OF TEA	Leau Sales	1933-12	nii imalietrios	in chart tame
Distribution of red	TOWN DWILLD,	2000 70,	og viladoli ico.	010 010010 00100

	Industry	1938	1939	1940	1941	1942
Storage batterie Paints Ceramics Other	98	19, 057 8, 698 655 1, 773	24, 709 11, 421 1, 123 2, 723	26, 718 11, 949 1, 117 2, 416	27, 405 20, 130 1, 593 4, 710	23, 545 21, 017 939 2, 868
		30, 183	39, 976	42, 200	53, 838	48, 369

Orange mineral.—This pigment is produced in very small quantities. The manufacture of ink has been its principal application in recent years. Restrictions were placed on its use for this purpose by the War Production Board, limiting consumption in the second quarter of 1942 to 70 percent of that used in one quarter in 1941. The above order was withdrawn in August.

Distribution of orange mineral sales, 1938-42, by industries, in short tons

Industry	1938	1939	1940	1941	1942
Ink manufacture	20 94 13	64 40 27	51 18 68	98 26 122	93 7 28
	127	131	137	246	128

Litharge.—Although sales of litharge in 1942 were 25 percent less than in 1941, they were the largest on record, except for that year. Over a period of years the use of litharge in storage batteries has shown an up-trend. Its use for this purpose in 1942 was less than in 1941 but above all earlier years. Consumption of litharge in insecticides was 24 percent less than in 1941, and except for 1938 it had been exceeded in every year from 1937 to 1941, inclusive. use in ceramics dropped 48 percent in 1942, but the quantity consumed in that year probably had not been exceeded before 1940. Chrome pigments fell 47, oil refining 29, and rubber 13 percent. Consumption of litharge in oil refining was only 4,771 tons in 1942, compared with 13,615 tons in 1929. In addition to the litharge used in the manufacture of batteries, the storage-battery manufacturers themselves make a black or suboxide of lead which they use as a substitute for litharge. Whereas the quantity so manufactured in 1942 (55,000 tons) was below the peak quantity (61,000 tons) in 1941, it equaled the former record level established in 1940. Black oxide figures are not included in the Bureau of Mines totals for litharge.

Distribution of litharge sales, 1938-42, by industries, in short tons

Industry	1938	1939	1940	1941	1942
Storage batteries. Insecticides Ceramies Chrome pigments Oil refining Rubber. Varnish Linoleum Other.	32, 514 11, 736 5, 889 5, 590 6, 411 880 2, 449 231 3, 011	39, 754 16, 435 8, 679 9, 415 7, 619 1, 404 2, 428 226 3, 558	38, 303 16, 041 12, 072 8, 456 6, 876 1, 590 3, 003 418 3, 082	49, 847 19, 403 18, 285 13, 927 6, 749 3, 968 3, 165 647 6, 289	43, 630 14, 830 9, 525 7, 344 4, 771 3, 460 3, 433 4, 187
	68, 711	89, 518	89, 841	122, 280	91, 513

Zinc oxide.—Zinc oxide production was affected adversely by the scarcity of zinc metal and scrap. Metal and scrap supplies have been restricted for several years; as a result, the proportion of zinc oxide made from ores has advanced sharply. Zinc oxide produced by the American process (from ore) accounted for 58 percent in 1936; it was 64 percent in 1940, 76 in 1941, and 84 in 1942. French process (from metal and scrap) meanwhile accounted for 42, 36, 24, and 16 percent, respectively, in those years. The proportion of French-process oxide made from scrap has also been on the up-trend. It amounted to 22 percent in 1936 and 45 in 1940 and 1941 but dropped back to 40 in 1942.

Total zinc oxide sales declined 33 percent in 1942, the amounts sold for use in rubber and ceramics showing the most severe drops. The

paint class performed better than all others.

Supplementary Order M-11-a was amended in May 1942 (effective June 1) to read that each producer of zinc oxide shall set aside from his production each month quantities to be determined from time to time by the Director of Industry Operations, the remainder to be distributed so that each customer would receive an equal percentage of the producer's commitments to him. For some time no zinc oxide has been set aside because of an excess already in the pool.

Distribution of zinc oxide sales, 1938-42, by industries, in short tons

Industry	1938	1939	1940	1941	1942
Rubber	46, 266 20, 884 3, 030 4, 908 4, 041	70, 187 25, 334 5, 641 6, 572 6, 818	70, 979 23, 268 4, 752 6, 352 7, 862	90, 429 30, 304 6, 991 8, 596 12, 513	52, 717 25, 122 5, 224 2, 934 13, 680
	79, 129	114, 552	113, 213	148, 833	99, 677

Leaded zinc oxide.—Sales of leaded zinc oxide declined 30 percent in 1942, which was almost as severe as the drop in sales of zinc oxide (lead-free). On the basis of long-time trends, however, it has fared far better than the lead-free class. Except for 1941, the leaded group was higher than in any other year and was 81 percent above the annual average for 1925–29. The lead-free class, on the other hand, was 35 percent below the 1925–29 average. Leaded zinc oxide is made entirely from ores, and although these supplies were not abundant they were notably larger than those for metal and scrap. Paint consumes virtually all of the leaded zinc oxide made. The figures for leaded zinc oxide include basic lead sulfate used in blending as indicated under "Basic lead sulfate."

Distribution of leaded zinc oxide sales, 1938-42, by industries, in short tons

Industry	1938	1939	1940	1941	1942
Paints Rubber Other	37, 348 868	41, 519 1 1, 164	44, 341 1, 021	67, 472 1 1, 447	47, 052 1, 076
	38, 216	42, 684	45, 362	68, 920	48, 128

Lithopone.—Lithopone statistics are reported on the basis of the regular lithopone content of high-strength lithopone plus normal lithopone sold as such. Lithopone sales in 1942 held up better than

「一」のでは、一時によるからないない。大学の教をなるないはないという

the average for the zinc-pigment group, having fallen 22 percent from 1941; sales for the year 1941 were close to the level for the 1925–29 period. The distribution of lithopone for paints—the principal use—dropped 18 percent in 1942 but was above the record for the total; sales for floor coverings and textiles were 25 percent lower and rubber 70 percent lower. Based on somewhat incomplete information, separation of the 1942 quantities shown in the following table for floor coverings and textiles indicates that 9,600 tons were used for linoleum and felt-base floor coverings and the remainder for coated fabrics and textiles (oil cloth, shade cloth, artificial leather, and similar products). Other sales in 1942 included 3,423 tons for paper and 555 (incomplete) for printing ink. Figures for an additional quantity for printing ink cannot be separated from the totals for paints. The principal item under "other" uses covers exports. One company, at least, has classified part of its exports according to the end use so that the "other" class is too small to cover total exports.

Plant capacity for the production of lithopone was reported to

total 182,000 tons at the end of 1942, unchanged from 1941.

Order M-128 of the War Production Board, issued in May 1942, provided for the establishment of a monthly producers' pool in zinc sulfide pigments, of which lithopone is the chief one. By the time the order had been completed, however, the situation had eased, and virtually no use was made of the power provided. The order is being kept on the books should it be needed.

Distribution of lithopone sales, 1938-42, by industries, in short tons

Industry	1938	1939	1940	1941	1942
Paints, etc. Floor coverings and textiles Rubber	101, 924 15, 400 3, 148 5, 274	113, 995 17, 429 3, 189 8, 146	1 117, 075 18, 738 3, 387 12, 602	1 132, 691 21, 114 3, 547 19, 290	1 109, 216 15, 775 1, 047 11, 282
	125, 746	142, 759	151, 802	176, 642	137, 320

<sup>&</sup>lt;sup>1</sup> Includes a quantity, not separable, used for printing ink.

The consumption of ordinary-strength lithopone in the manufacture of titanated lithopone (which usually contains 15 percent TiO<sub>2</sub>) reached a peak in 1937, when 19,400 tons were so used; this use took only about half of the record amount, or 9,900 tons in 1942. The lithopone figures in the following table are included in the totals for ordinary lithopone in the preceding table.

Titanated lithopone produced in the United States and ordinary lithopone used in its manufacture, 1938-42, in short tons

Year	Titanated lithopone produced	Ordinary lithopone used	Year	Titanated lithopone produced	Ordinary lithopone used
1938 1939 1940	20, 100 16, 100 18, 100	17, 000 13, 700 15, 200	1941 1942	16, 800 11, 700	14, 100 9, 900

Zinc sulfide.—In recent years as many as four plants have reported production of zinc sulfide, but one company has always dominated the production. For that reason the Bureau of Mines is not at liberty to publish the figures for this pigment. Only this one company produced in 1942.

Zinc chloride.—Sales of zinc chloride, in terms of 50° B. solution, totaled 52,374 tons in 1942. These figures include the zinc chloride equivalent of zinc ammonium chloride and chromated zinc chloride produced. Comparable data for recent earlier years are not available.

Zinc sulfate.—Although sales of zinc sulfate declined 25 percent from 1941, they were the highest ever recorded, except for that year. reason for the recent records for this salt is its increasing use for agricultural purposes. This use made noteworthy gains in 1942 as against the declines in most other uses. Much less zinc sulfate was consumed in the manufacture of rayon, chemicals, and glue in 1942 than in 1941, but the amounts so used compared favorably with other years. Consumption of zinc sulfate in paint and varnish processing has been increasing rapidly in recent years, and it reached new heights in 1942 when it rose 35 percent over 1941. Its use as a flotation reagent has also been gaining.

The large quantity of zinc sulfate produced as an intermediate product in the manufacture of lithopone is excluded from the zincThe state of the s

sulfate statistics.

Distribution of zinc sulfate sales, 1938-42, by industries, in short tons

Industry	1938	1939	1940	1941	1942
Agriculture	1, 664 2, 851 947 656 285 63 .284 59	2,168 3,897 1,309 583 172 266 556	2, 366 3, 649 2, 151 1, 509 320 241 348 54 1, 299	3, 038 5, 170 5, 555 1, 422 1, 203 312 502 130 1, 869	4, 123 3, 149 2, 595 1, 917 750 355 219 60 1, 163
	7, 757	10, 157	11, 937	19, 201	14, 331

### RAW MATERIALS USED IN MANUFACTURE OF LEAD AND ZINC PIGMENTS AND ZINC SALTS

Lead pigments and zinc pigments and salts are manufactured from a variety of materials, including ore, refined metal, and such miscellaneous secondary materials as scrap and waste from various industrial In 1942, 93 percent of the lead pigments was derived from pig lead and 7 percent from ore. A small part of the ore used was foreign. The proportion for zinc pigments in 1942 was 79 percent from ore, 6 percent from slab zinc, and 15 percent from secondary materials; 9 percent of the ore used was foreign.

Metal content of lead and zinc pigments produced by domestic manufacturers, 1941-42, by sources, in short tons

00, 000 00000				
19	41	1942		
Lead in pig- ments <sup>1</sup>	Zinc in pig- ments	Lead in pig- ments <sup>1</sup>	Zinc in pig- ments	
23, 951 290 248, 674 400	129, 520 2, 464 15, 463 31, 703	15, 949 707 206, 680 2	103, 445 9, 636 8, 252 21, 663	
273, 315	179, 150	223, 338	142, 996	
	19 Lead in pig- ments 1  23, 951 290 248, 674 400	23, 951 129, 520 290 2, 464 248, 674 15, 463 31, 703	1941 19  Lead in pigments 1 Zinc in pigments 1  23, 951 129, 520 15, 949 290 2, 464 707 248, 674 15, 463 206, 680 31, 703 2	

Includes also lead recovered in leaded zinc oxide.
 Zinc ashes, skimmings, drosses, and old metal.

The following tables give the source of the metal used in the manufacture of each pigment and salt. Pig lead is employed exclusively, either directly or indirectly, in the manufacture of white lead, litharge, red lead, and orange mineral and is used also in the manufacture of basic lead sulfate. The lead content of leaded zinc oxide made from basic lead sulfate, which in turn was made from pig lead, is credited to pig lead in the table. Zinc oxide is the only pigment in which considerable slab zinc is used. Ore is employed in the manufacture of zinc oxide, leaded zinc oxide, lithopone, zinc sulfate, and basic lead sulfate. A substantial proportion of the zinc in lithopone and most of that in zinc chloride made in the United States are derived from secondary material. A decided increase has been noted in the quantity of secondary zinc consumed in the manufacture of zinc oxide The scarcity of zinc metal and scrap in 1942 caused declines in the proportions of zinc oxide made from these two materials in that year.

Lead content of lead and zinc pigments produced by domestic manufacturers, 1941-42, by sources, in short tons

			1941			1942				
Pigment	Lead in pigments produced from—				Lead in pigments produced from—					
		Ore		Second-	Total lead in pig-	О	re		Second-	Total lead in pig-
	Do- mestic	For- eign	Pig lead	ary ma- terial	ments	Do- mestic	For- eign	Pig lead	ary ma- terial	ments
White lead			86, 750 47, 615 112, 099 172		86, 750 47, 615 112, 099 172			73, 757 45, 228 86, 667 81		73, 757 45, 228 86, 667
Basic lead sulfate Leaded zinc oxide	6, 122 17, 829	290	1, 126 912	400	7, 648 19, 031	4, 760 11, 189	707	827 120	2	5, 587 12, 018
	23, 951	290	248, 674	400	273, 315	15, 949	707	206, 680	2	223, 338

Zinc content of zinc pigments and salts produced by domestic manufacturers, 1941-42, by sources, in short tons

			1941			1942					
Pigment or salt	Zinc in pigments and salts produced from—			Total zinc in	Zinc in pigments and salts produced from—				Total		
	0	re	Slab	Second- ary ma- terial	pig- ments	0	re	Slab	Second-	zinc in pig- ments and	
	Domes- tic	Foreign	zine   E		colta	Domes- tic	Foreign	zinc	ary ma- terial <sup>1</sup>	salts	
Zinc oxide Leaded zinc oxide Lithopone Zinc sulfide Zinc chloride Zinc sulfate	87, 999 27, 508 14, 013 (2) (2) 2, 831	373 2,091	15, 435 28 (²)	12, 826 1, 469 17, 408 	116, 633 31, 068 31, 449 (2) (2) (2) 5, 671	74, 289 19, 687 9, 469 (²) 671	313 5, 555 3, 768 (²) 1, 250	8, 247 5 10 36	5, 585 328 15, 750 11, 777 2, 151	88, 434 25, 570 28, 992 (2) 11, 787 4, 108	

<sup>&</sup>lt;sup>1</sup> These figures are higher than those shown in the report on Secondary Metals—Nonferrous because they include zinc recovered from byproduct sludges, residues, etc., not classified as purchased scrap material.

<sup>2</sup> Data not available.

#### PRICES

The total and average values reported by producers for lead and zinc pigments are given in the tables in the first part of this report. For all of the lead pigments average values were \$9 to \$32 a ton higher than in 1941; the small-tonnage orange mineral gained \$5. All of them were at their lowest points for the year in January, which coincided with the highest levels attained in 1941. For each pigment, except basic lead sulfate (white), the gains in 1942 amounted to % cent a pound. In general, the high points were reached in the first 2 months, and prices continued at these levels for the remainder of the year and beyond. Litharge did not reach a peak until June. Basic sulfate (white) advanced % cent in April and dropped back ¼ cent in July.

Pig lead, price changes for which are usually followed closely by those for lead pigments, was under ceiling price limitations beginning January 1942. The ceiling price for common lead, delivered New York, was 6.50 cents a pound. Corroding lead and chemical lead

were allowed premiums of 0.10 cent a pound.

Average values reported for all zinc pigments sold were also higher in 1942, the gains ranging from \$13 a ton for zinc oxide to \$8 for litho-The average value for zinc sulfate rose \$8 a ton in 1942. voluntary price ceilings on zinc oxide agreed to by producers, following requests in December 1941 from the Office of Price Administration, were given in the chapter of this series for 1941. On the whole, prices throughout 1942 were % cent a pound above those of the previous Late in March negotiations were carried on to increase the voluntary ceilings on leaded zinc oxide containing 35 percent or more lead to 7 cents a pound. The proposed increase was caused by advances in the price of basic sulfate, a basic ingredient of leaded zinc oxide. Later in the month the sweeping General Maximum Price Regulation gathered all grades of zinc oxide among other chemicals, oils, paints, and other commodities under its provisions. Prices under the Regulation were not to exceed the highest ones prevailing in March In June the Office of Price Administration established the maximum price of 7 cents a pound for the leaded grade mentioned above, effective June 22. Later the effective date was moved back to May 11. A premium of \( \) cent a pound was permitted for delivery of oxide in barrels, another 1/4 cent for delivery of less than carlots, and an additional ½ cent for delivery in less than carlots to consumers in California, Oregon, or Washington. Price Schedule 80 of the Office of Price Administration, effective February 2, 1942, set a maximum price of 4.25 cents a pound for the normal grade of lithopone.

Range of quotations on lead pigments and zinc pigments and salts at New York (or delivered in the East), 1939-42, in cents per pound

Product	1939	1940	1941	1942
Basic lead sulfate, or sublimed lead, less than carlots, barrels	6, 25- 6, 50	6. 25- 6. 75	6, 50- 7, 00	7.00- 7.75
White lead, or basic lead carbona dry, carlots, barrels.		7.00- 7.50		
Litharge, commercial, powdered, barrels	6.25-7.75			
Red lead, dry, 95 percent or less, less than carlots, barrels.				
Orange mineral, American, small lots, barrelsZinc oxide:			11.00-11.75	
American process, lead-free, bags, carlots	6. 25- 7. 50			7.25
American process, 5 to 35 percent lead, barrels, carlots.	6. 25- 6. 38			
French process, red seal, bags, carlots	7.50			
French process, green seal, bags, carlots				
French process, white seal, barrels, carlots	8.75	8.75- 9.00		
Lithopone, domestic, 5-ton lots, bags	4.00-4.38			
Zinc sulfide, less than carlots, bags, barrels	7.75-8.88	7.75-8.00	8.00- 8.25	8.50-8.75
Zinc chloride, works:				
Solution, tanks	2. 25		2. 25- 2. 50	
Fused, drums	4. 25- 5. 75		4. 25- 6. 50	
Zinc sulfate, crystals, barrels	2.90- 3.65	2.90-3.90	3. 15- 4. 40	3.65-4.60

### FOREIGN TRADE 4

All of the most important items in foreign trade in lead and zinc pigments are in the export classification and cover white lead, red lead, litharge, zinc oxide, and lithopone. Except for the items specified, foreign trade in lead and zinc pigments has little significance. Exports of all of the important pigments in 1942 declined sharply from the previous year but compared favorably with the years immediately preceding 1941. Available data on imports and exports appear in the following tables.

Value of foreign trade of the United States in lead and zinc pigments and salts, 1941-42

	19	<b>141</b>	1942		
	Imports	Exports	Imports	Exports	
Lead pigments:					
White lead	\$389 250	\$419, 630 437, 786 370, 934	\$182 432	\$392, 812 257, 921 289, 940	
Orange mineral Other lead pigments	11, 694	(1)	3, 221	1, 887 14, 600	
	12, 333	1, 228, 350	3, 835	957, 160	
Zine pigments: Zine oxide	19,756 9 1,866	1, 446, 157 2, 079, 229 (¹)	6, 128 1, 677	1, 001, 248 1, 732, 898 6, 328	
	21, 631	3, 525, 386	7, 805	2, 740, 474	
Lead and zinc salts: Lead arsenate	3, 034 8, 204 (1)	871, 985 (1) (1) (1) (1) (1)	2,006 18,585 (¹)	73, 312 (1) 42, 674 53, 624 76, 023	
	11, 238	871, 985	20, 591	245, 633	
Grand total	45, 202	5, 625, 721	32, 231	3, 943, 267	

<sup>1</sup> Data not available.

<sup>&</sup>lt;sup>4</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

### Lead pigments and salts imported for consumption in the United States, 1938-42

Year	Basic carbonate white lead	Red lead	Litharge	nge © ral	Lead com- pounds	Total value
1938	20 11 2	1 2	(2)	2 1	85 104	1 \$22, 644 1 28, 248 1 13, 969
1941 1942	2	3 2	2		17 11	1 15, 367 1 5, 841

<sup>&</sup>lt;sup>1</sup> Includes also—1938: Lead pigments, n. s. p. f., \$198 (2,330 pounds), and suboxide of lead, n. s. p. f., \$5,335 (31,334 pounds); 1939: Lead pigments, n. s. p. f., \$600 (5,270 pounds), and suboxide of lead, n. s. p. f., \$6,620 (40,445 pounds); 1940: Suboxide of lead, n. s. p. f., \$13,571 (71,148 pounds); 1941: Suboxide of lead, n. s. p. f., \$11,694 (65,268 pounds); 1942: Suboxide of lead, n. s. p. f., \$3,221 (13,228 pounds).

<sup>2</sup> Less than 1 ton.

### Lead pigments and salts exported from the United States, 1938-42

			Shor	t tons			Total
Year	White lead	Red lead	Litharge	Orange mineral	Sublimed lead	Lead arsenate	value
1938. 1939. 1940. 1941.	1, 411 2, 024 1, 360 2, 901 2, 249	806 1, 324 1, 336 2, 966 1, 391	1, 694 2, 077 1, 586 2, 892 1, 999	(1) (1) (1) (1) 7	(1) (1) (1) (1) 95	511 856 1,450 4,797 296	\$605, 075 875, 235 836, 230 2, 100, 335 1, 030, 472

<sup>&</sup>lt;sup>1</sup> Not compiled on an annual basis prior to 1942.

### Zinc pigments and salts imported for consumption in the United States, 1938-42

	Short tons							
Year	Zinc oxide		Litho-	Zinc	Zinc	Zinc	Total value	
	Dry	In oil	pone	sulfide	chloride	sulfate		
1938	579 1, 485 273 122 13	66 66 45 11	3, 932 2, 641 (¹)	(1) 12 7 1 1	272 399 19	392 325 245 162 362	\$321, 445 317, 719 54, 923 29, 835 26, 390	

<sup>1</sup> Less than 1 ton.

### Zinc pigments and salts 1 exported from the United States, 1938-42

	Short tons				Short		
Year	Zinc oxide	Litho- pone	Total value	Year	Zinc oxide	Litho- pone	Total value
1938 1939 1940	1, 163 3, 485 3, 239	1, 734 4, 845 14, 298	\$339, 415 925, 468 1, 584, 667	1941 1942	8, 264 6, 013	21, 527 17, 036	\$3, 525, 386 2 2, 912, 795

 <sup>&</sup>lt;sup>1</sup> Zinc salts not separately recorded on an annual basis prior to 1942.
 <sup>2</sup> Includes also: Zinc sulfide \$6,328 (37,691 pounds); zinc chloride, \$42,674 (648,343 pounds); zinc sulfate, \$53,624 (1,025,554 pounds); other zinc salts and compounds, \$76,023 (592,029 pounds).

### GOLD, SILVER, COPPER, AND LEAD IN ALASKA

(MINE REPORT)

By Chas. W. Henderson

#### SUMMARY OUTLINE

	Page		Page
Summary	219	Markets and metallurgy	222
Calculation of value of metal production	219	Review by regions	223

### SUMMARY

Gold recovered from Alaska ores and gravels in 1942 totaled 487,621 fine ounces valued at \$17,066,735, compared with 695,467 ounces valued at \$24,341,345 in 1941. The value of the gold in 1942, as in 1941, was 99 percent of the total gross value of the gold. silver. copper, and lead produced. The silver, lead, and copper produced were byproducts of gold mining. The number of producing lode mines decreased from 56 in 1941 to 38 in 1942, floating connectedbucket dredges from 47 to 31, and other types of placer operations from 752 to 422.

The outbreak of the war in December 1941 affected Alaska mining enterprises, both large and small, in several ways and, in a broad sense, is virtually responsible for the decrease in metal output of Alaska lode and placer mines. The threat of enemy invasion prompted the expenditure of hundreds of millions of dollars for highways, airfields, pipe lines, Navy bases, Army cantonments, and other construction necessary for the defense of the Territory. The high wages offered laborers on these projects lured many mining men from their positions at the mines and created a serious labor shortage which closed several of the lode mines, kept certain dredging operations from opening in 1942, and forced all mining operations to work shorthanded. Dragline operators whose property remained closed or who were unable to finish the 1942 season had no trouble in disposing of their equipment to contractors on Government defense projects.

War Production Board Gold Mining Limitation Order L-208, coming as it did on October 8, had very little effect on metal production in Alaska in 1942, inasmuch as the mining season for all placer mines and dredges and most lode mines usually ends in November. full brunt of the order will be felt in 1943. All dredging except the Goodnews Bay platinum operations has ceased for the duration of Only three important lode mines were active the first half of 1943, and these were permitted only under limited reprieves.

All tonnage figures are short tons and "dry weight"; that is, they

do not include moisture.

Yardage figures used in measuring material treated in placer operations are "bank measure"; that is, the material is measured in the ground before treatment.

The value of metal production herein reported has been calculated

at the following prices.

### Prices of gold, silver, copper, lead, and zinc, 1938-42

	Year	Gold 1	Silver 2	Copper 3	Lead 4	Zinct
1938 1939 1940 1941		Per fine ounce \$35.00 35.00 35.00 35.00	Per fine ounce 5 \$0.646+ 6.678+ 7.711+ 7.711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057	Per pound \$0.048 .052 .063 .075 .093

1 Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.

2 Treasury buying price for newly mined silver.

3 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for overquota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.

4 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for overquota production.

A TOTAL SOLD THE STATE OF THE S

\$ \$0.64646464. 6 \$0.67878787. 7 \$0.71111111.

The following tables show the mine production of gold, silver, copper, and lead in Alaska in 1938-42 and 1880-1942 in terms of recovered metals; the output of gold and silver in 1942, by types of operation; and the output of gold, silver, copper, and lead from amalgamation and cyanidation mills (with or without concentration equipment) in 1942, by regions.

Mine production of gold, silver, copper, and lead in Alaska, 1938-42, and total, 1880-1942, in terms of recovered metals

Year	Gold (lode	and placer)	Silver (lode and placer)		
ICAL	Fine ounces	Value	Fine ounces	Value	
1938 1939 1940 1941 1942	664, 973 676, 737 755, 970 695, 467 487, 621	\$23, 274, 055 23, 685, 795 26, 458, 950 24, 341, 345 17, 066, 735	479, 853 201, 054 191, 679 191, 522 119, 704	\$310, 208 136, 473 136, 305 136, 193 85, 123	
1880-1942	25, 639, 651	610, 402, 387	19, 682, 372	14, 000, 794	

Year	Cor	per	Le	Matal l		
lear	Pounds	Value	Pounds	Value	Total value	
1938 1939 1940 1941 1942	29, 098, 000 256, 000 110, 000 144, 000 44, 000	\$2, 851, 604 26, 624 12, 430 16, 992 5, 324	1, 988, 000 1, 874, 000 1, 558, 000 1, 324, 000 830, 000	\$91, 448 88, 078 77, 900 75, 468 55, 610	\$26, 527, 315 23, 936, 970 26, 685, 585 24, 569, 998 17, 212, 792	
880-1942	1 685, 830	226, 554, 306	1 24, 556	2, 710, 631	853, 668, 118	

<sup>1</sup> Short tons.

THE RESERVE OF THE PARTY OF THE

Mine production of gold and silver in Alaska in 1942, by types of operation, in terms of recovered metals

			Gold			Silver			
Type of operation	Mines pro- ducing	Material treated	Fine		ent of tal	Fine	Perce	ent of tal	Total value
			ounces	1942	1941	ounces	1942	1941	
Lode mines	38	1 2, 816, 668	137, 499	28	29	68, 798	57	65	\$4,861,388
bucket dredges Placers (dragline and dry- land dredges, hydraulic, drift mining, and sluic-	31	<sup>3</sup> 15, 684, 520	249, 868	51	44	34, 695	29	20	8, 770, 052
ing)	3 422	(4)	100, 254	21	27	16, 211	14	15	3, 520, 418
Total, 1941	491 855		487, 621 695, 467	100	100	119, 704 191, 522	100	100	17, 151, 858 24, 477, 538

Short tons of ore.
 Cubic yards of gravel (average recovered per yard, \$0.56).
 Includes all types and sizes of placer operations, excluding floating connected-bucket dredges.
 Cubic yards of gravel; figures not available.

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in Alaska in 1942, by regions, in terms of recovered

		Recovered in bullion		Concentrates smelted and recovered metal				
Region	Ore treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Con- cen- trates pro- duced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)
Cook Inlet-Susitna Copper River Kenai Peninsula Kuskokwim	32, 389 1, 420 587 (1)	30, 705 1, 703 554 148	1,628 359 154 35	1, 119 88 2	6,844 353 40	573 106 28	4, 200 200	100 160
Southeastern Alaska Yukon River Basin	2, 770, 434 10, 054	68, 094 14, 100	16, 780 2, 972	1,586 67	14, 353 378	44, 196 469	37, 437	798, 849 1, 100
Total, 1941	2, 814, 884 4, 443, 260	115, 304 165, 530	21, 928 31, 823	2, 862 3, 963	21, 968 33, 451	45, 372 81, 697	41,837 78,901	800, 209 1, 322, 13

1 Less than 1/4 ton.

Gold.—Floating connected-bucket dredges recovered 51 percent of the total Alaska output of gold in 1942 compared with 44 percent in The United States Smelting, Refining & Mining Co., operating seven dredges in the Fairbanks district and two in the Nome district, was the largest producer of gold from this source in the Territory in both years. Placer mines worked by dragline and dry-land dredges, bulldozers, and hydraulic giants, drifting, and sluicing together yielded 21 percent of the total gold in 1942 compared with 27 percent in 1941. A large part of the output from these types of operations came from the Fairbanks, Circle, Council-Bluff, Iditarod (Flat), Fairhaven, Tuluksak-Aniak, and Nome districts. Lode mines contributed 28 percent of the total Alaska output of gold in 1942 compared with 29 percent in 1941. The Alaska Juneau Gold Mining Co. continued to be much the largest producer of lode gold in Alaska.

Silver.—All the silver produced in Alaska in 1942 was a byproduct

of gold mining.

Copper.—The output of recoverable copper in Alaska in 1942 came

from dry and siliceous ores.

Lead.—Most of the recovered lead output of Alaska in 1942 came from lead concentrates produced at the flotation mill of the Alaska Juneau Gold Mining Co.

### MARKETS AND METALLURGY

About 95 percent of the gold and 61 percent of the silver produced from Alaska ores and gravels in 1942 were obtained in the form of gold-silver bullion, which was sold finally to the Seattle Assay Office and the San Francisco Mint. As there are no smelters or refineries in Alaska, all the remaining gold and silver produced and all the lead and copper were obtained from high-grade ore and concentrates shipped to smelters and refineries in the States, largely to the Tacoma (Wash.) and Selby (Calif.) smelters. The largest purchasers (or agents) of gold-silver bullion in the Territory and in Seattle (Wash.) in 1942 were: The Bank of Alaska, Anchorage; the Bank of Fairbanks and the First National Bank of Fairbanks, Fairbanks; the First National Bank of Valdez, Valdez; the Miners and Merchants Bank of Alaska, Nome; the Miners and Merchants Bank of Iditarod, Flat; and the Northern Commercial Co., Seattle, Wash. The bullion purchased was either sent direct to the mints or cast into bars for shipping; in many instances the banks acted merely as agents for the lode and placer operations.

Ore-dressing mills active in Alaska in 1942 included the 12,000-ton Alaska Juneau amalgamation-table concentration-flotation mill and and approximately 31 other mills, chiefly amalgamation or cyanidation plants, a few of which have some other supplementary concentrating equipment. With the exception of the Alaska Juneau, no mill had a daily capacity of over 75 tons. Virtually all the lead concentrates produced in 1942 were obtained from concentration by flotation of the dry gold ore of the Alaska Juneau Gold Mining Co. property at Juneau. Most of the small output of copper also came from lead concentrates produced at the Alaska Juneau property. Shipments of concentrates from amalgamation or cyanidation mills having concentrating equipment averaged 7.68 ounces of gold and 15.85 ounces of silver to the ton; concentrates from straight concentration mills averaged 1.58 ounces of gold and 10.54 ounces of silver to the ton. Many mills reported mill heads averaging more than 1 ounce of gold to the ton.

Bullion of Alaska origin deposited at United States Assay Office, Seattle, Wash., during year ended December 31, in fine ounces

		19	41		
District	Gold	Silver 1	District	Gold	Silver 1
Circle Cook Inlet Copper River Eagle Iditarod Koyukuk	16, 497 49, 457 7, 322 3, 252 73, 652 5, 956	1,775 4,616 1,205 6,921 4,664 774	Kuskokwim Nome Southeastern Alaska Tanana <sup>3</sup>	27, 323 133, 034 106, 180 207, 740 630, 413	3, 289 14, 418 24, 139 32, 796 94, 597
		19	42		
Region	Gold	Silver	Region	Gold	Silver
Cook Inlet-Susitna Copper River Kenai Peninsula Kuskokwim	35, 611 3, 761 12 16, 543	2, 500 565 3 1, 666	Seward Peninsula Southeastern Alaska Yukon River Basin	68, 116 71, 069 268, 579 463, 691	7, 723 17, 309 42, 370 72, 136

<sup>1</sup> Revised figures.

Includes manily Bonnifield, Fairbanks, Hot Springs, Kantishna and Tolovana districts in the Yukon Basin region.

The second secon

11日

### REVIEW BY REGIONS

Cook Inlet-Susitna region.—This region, which includes the Iliamna, Valdez Creek, Willow Creek, and Yentna-Cache Creek districts, produced 27 percent of the total gold output from lode mines in Alaska in 1942. There were 7 producing lode mines compared with 10 in 1941.

The Alaska-Pacific Consolidated Mining Co., operating the Independence, Martin, Free Gold, and Ready Bullion mines near the head of Fishhook Creek in the Willow Creek district, continued to be the largest producer of gold in the Cook Inlet-Susitna region and the second-largest producer of lode gold in Alaska. The company 72-ton amalgamation-flotation mill and sorting plant were operated at capacity 7 days a week throughout the year. The ore treated averaged 1.34 ounces of gold and 0.48 ounce of silver to the ton. Because the ore contains scheelite, the War Production Board in November issued a special permit which enabled the company to continue its gold operations until midsummer of 1943. At that time, the exact quantity of scheelite will have been determined and necessary alterations for its recovery will have been made in the mill. The new installation will include 2 sand tables, slime decks, and 16 flotation cells. As the tailings assays from the gold-recovery operations show a scheelite content of 0.5 to 2½ percent, the mill procedure will be first to recover the gold, the tailing to be treated subsequently on tables and finally by flotation to produce tungsten concentrates.

The Willow Creek Mining Co. operated its Lucky Shot, War Baby, and Gold Bullion mines and 60-ton amalgamation-flotation-cyanidation mill on Craigie Creek, 22 miles north of Wasilla, until September 1942, when it ceased operations because of an acute shortage of labor. Methods of ore treatment are described in the Alaska chapter of

Minerals Yearbook, 1941.

Other lode-gold producers in the Cook Inlet-Susitna region were the Fern Gold Leasing Co., operating its Fern and Talkeetna group of mines and 30-ton amalgamation-flotation mill; and the Gold Cord Mining Co., operating the Gold Cord lode and 20-ton amalgamationflotation mill, and Gold Zone Mine, Inc., both of which closed in

August because of labor shortage.

Placer operations, using principally hydraulic giants, continued to recover gold from stream and bench gravels. Placer production in the Yentna-Cache Creek district came from property around the Dutch and Peters Hills, part of the southern foothills of the Alaska Range. The productive placer creeks flowing from these hills are tributaries of Peters, Cache, or Granite Creeks. Among the larger producers of placer gold in the district were the Fairview Mining Co., C. M. Reeve & Son, Falls Creek Mining Co., and Talkeetna Mines, Inc. In the Valdez Creek district John E. Carlson worked several placers on Valdez Creek.

Copper River region.—The Copper River region includes the Chistochina, Nelchina, Nizina, Prince William Sound, and Yakataga (including Icy Bay) districts. Cliff Goldmines, Inc., operated the Cliff mine and 24-ton amalgamation-gravity concentration mill on Valdez Bay, 10 miles west of Valdez, until October, when operations ceased owing to inability to obtain sufficient supplies, equipment, and labor. Improvements at the mine in 1942 included installation of an electric hoist, a ventilating fan on the 500-foot level, and a telephone

communication system servicing all sections of the mine. In 1942 the property produced bullion yielding 1,617 fine ounces of gold and 338 fine ounces of silver, and 51 tons of gold-silver concentrates containing 78 ounces of gold and 22 ounces of silver. Other producers of lode gold included the Sun Ray Mining Co. and Don C. Preston, both operating in the Prince William Sound district. Yellow Band Gold Mines, Inc., was unable to open its property in the Nizina district in 1942 because of the War Production Board amendment to Order P-56 depriving gold and silver mines of an effective priority rating for obtaining equipment and supplies.

Placer gravels were worked in the Copper River region in 1942 chiefly by hydraulicking and ground sluicing. Larger placer-gold producers included Chititu Mines in Rex Gulch and Dan Creek Placer Mines, Inc., on Dan Creek 25 miles east of McCarthy in the Nizina district.

Kenai Peninsula region.—The Kenai Peninsula region includes the Moose Pass-Hope, Nuka Bay-Homer, and Turnagain Arm-Girdwood districts. Most of the output of lode gold in the Kenai Peninsula region came from the Marigold and Gilpatrick mines near the divide between Quartz and Canyon Creeks in the Moose Pass-Hope district; the Paystreak mine in the Nuka Bay-Homer district; and the Crow Creek Gold Corporation property at the head of Crow Creek in the Turnagain Arm-Girdwood district. Among the producing placers were the Hope Mining Co. on Resurrection Creek and Stetson Placers, Inc., on Stetson Creek in the Moose Pass-Hope district.

Kuskokwim region.—The Kuskokwim region includes the Bethel, Goodnews Bay, McGrath, and Tuluksak-Aniak mining districts. A clean-up of the mill at the Nixon Fork mine, owned and operated by Mespelt & Co., produced a small quantity of gold bullion, which was

sold to the Seattle Assay Office.

In the Goodnews Bay district, the Goodnews Bay Mining Co., dredging for platinum, operated its dredge (equipped with 92 8-cubic foot buckets) on Salmon River from April 25 to November 10. The company also produced platinum from its dragline operations on Salmon River. The New York Alaska Gold Dredging Co. operated its two floating connected-bucket dredges (one with 4-cubic foot buckets and the other with 2½-cubic foot buckets) from May 9 to November 14 at its consolidated group of placer claims on upper Tuluksak River in the Tuluksak-Aniak district.

Larger producers of placer gold from dragline land dredge operations included the Marvel Creek Mining Co. and Garrison Co. in the Tuluk-

sak-Aniak district.

Northwestern Alaska region.—A small quantity of placer gold was

recovered by sluicing on the Kobuk River in 1942.

Seward Peninsula region.—Mining in the Seward Peninsula region—comprising the Council-Bluff, Fairhaven, Kougarok, Koyuk, Nome, Port Clarence, and Serpentine River districts—was confined to the recovery of placer gold. The region had 14 floating connected-bucket dredges in 1942 (compared with 22 in 1941) and numerous bulldozer, hydraulicking, dragline land dredging, drift mining, and ground-sluicing operations. A total of 4,228,071 cubic yards of gravel containing 52,528 fine ounces of gold and 5,960 fine ounces of silver was handled by the dredges of the region. The average value of the gravel worked by dredges was about 44 cents per cubic yard compared with 47 cents in 1941.

THE PARTY OF THE PROPERTY OF THE PARTY OF TH

The United States Smelting, Refining & Mining Co., in the Nome district, was again the largest producer of gold in the region. The company operated two electrically powered Yuba dredges (one with 134 and one with 112 9-cubic foot buckets) from May 26 to October 15. Gravel washed in 1942 totaled 2,413,450 cubic yards compared with approximately 4,000,000 in 1941.

Arctic Circle Exploration, Inc., operated two dredges, each with 70 4-cubic foot buckets, on Candle Creek in the Fairhaven district and

again ranked second in production of gold in the region.

Lee Bros. Dredging Co., third-largest producer of placer gold in the region, operated two Diesel-powered floating connected-bucket dredges (one with 74 and one with 66 buckets) on the Solomon River in the Nome district from June to October.

Castleton & Keenan operated a Washington Iron Works Dieselpowered dredge equipped with 85 2½-cubic foot buckets on the Kougarok River in the Kougarok district from May 15 to October 6.

Other companies operating floating connected-bucket dredges in the Seward Peninsula region were: The Alaska Placer Co., Camp Creek Dredging Co., and Inland Dredging Co., all in the Council-Bluff district; Dry Creek Dredging Co. and Forsgren Dredging Co., both operating on the Inmachuk River in the Fairhaven district; Fox Bar Dredging Co. in the Kougarok district; and Casa de Paga Gold Co. on Beaver Creek in the Nome district.

Larger producers of gold from placers worked by hydraulic giants, with some additional combination of bulldozers, draglines, and pumping equipment, were: Crabtree & Sullivan in the Council-Bluff district; Mud Creek Mines in the Fairhaven district; Castleton & Keenan, Dahl Creek Mining Co., Gold Bullion, Inc., and Grant Mining Co., all in the Kougarok district; B. F. Gillette, Gabe Johnson & Co., and E. W. Quigley in the Nome district; and Frank L. Rice and Gilbert Fidjeland in the Port Clarence district.

Southeastern Alaska region.—Southeastern Alaska—including the Admiralty Island, Chichagof Island, Hyder, Juneau, Ketchikan, and Windham Bay districts—produced 60 percent of the total lode gold and most of the silver, copper, and lead output of Alaska as a whole in 1942. There were 12 active mines in 1942 compared with 16 mines

in 1941.

The Alaska Juneau was the largest producer of silver and lead and was second only to the United States Smelting, Refining & Mining Co. in output of gold in Alaska in 1942. In the Twenty-Eighth Annual Report of the Alaska Juneau Gold Mining Co., for the year ended December 31, 1942, the president's report (dated March 4, 1943) says—

On October 8, 1942, there was issued by the War Production Board in Washing ton, "Limitation Order L-208," the purpose of which was to close down "in the shortest possible time" all "nonessential mine" operations, with particular reference to gold mines. The purpose of the order was the freeing of labor for use in mining those metals needed for war purposes. There were certain exceptions embraced in the order which made it possible for the Alaska Juneau mine to continue operating on a limited scale. It so happens also that your company's operations, taken as a single unit, are of such value in the supplying of many indispensable services to the Juneau community and to the military and naval forces located therein, as to far outweigh any benefits that might arise through their discontinuance. The release of manpower contemplated by the order could only be small for the reason that our crew has already become reduced from a normal

full production working crew of about 1,000 men to the present crew of 350 men, the employees having been drawn away by higher wages offered in the war indus-

tries than the company can afford to pay.

With this curtailed crew it is still possible to make a small operating profit. It may be considered, of course, that operation at this reduced capacity is merely a matter of exhausting our ore reserves to no point, but as against this view it must be considered that a complete shut-down would not only involve a very considerable standby expense but would also result in the loss of many of our key men whose training, experience, and general efficiency is a highly essential factor in the successful operation of the Alaska Juneau mine. If, for some reason arising out of the present emergency, mining had to be discontinued altogether, then resumption at a later date with a crew of men green to the operation and unacquainted with each other, would have a decided adverse effect on the smooth and efficient handling of the property. From all points of view, therefore, it is most fortunate that the operations have been continuous throughout even on a limited scale; although, as far as can now be foreseen, there will be no change in the situa-

tion until the present emergency has terminated.

There has been no important change in the mine or in the plant during the past year as, owing to the scarcity of labor, no new work of any kind has been undertaken; in fact, the operations have consisted of merely marking time with

all effort being made to prevent an operating loss.

As was stated in the annual report for last year, there has been an attempt made to find profitable mining ventures in the strategic minerals field, and, while much work was done in this direction and many properties examined, nothing worth while has been found. This exploratory work, however, still continues. During the year some plans were entered into with the Metals Reserve Co., an agency of the Federal Government, for the treatment of Alaska chrome ores in our mill at Juneau, but upon investigation they have decided that the physical obstacles involved did not justify going ahead with these plans, particularly in view of the large increase in the production of chrome from other sources where conditions for cheap operations were much more favorable.

The general superintendent's report (dated February 1, 1943)

The present war has greatly interfered with the operation of the mine. During the year 1942, the amount of rock trammed from the mine was 2,765,190 tons as compared to the previous year's output of 4,354,770. The difference represents

a decrease of about 4,400 tons per day on the average. The North ore body furnished 20 percent of the year's tonnage, the South ore body 23 percent, while the Perseverance division of the mine supplied 57 percent of the total.

During the year 235,750 pounds of powder were used in blasting powder drifts, or 0.09 pound per ton trammed. Total powder consumption for primary and secondary breaking was 0.28 pound per ton trammed in 1942, as against 0.29 pound in 1941 and 0.32 pound in 1940. This gives a tonnage ratio of 3.55 tons of ore per pound of powder in 1942, as against 3.45 tons in 1941.

The past year also saw a great reduction in the amount of development and

The past year also saw a great reduction in the amount of development and preparatory mining work. During the year, however, the main haulage level on 13 level in the Deep North ore body was completed between the main shaft and the principal oreway. All exploratory work has been discontinued.

In June the operation of the mine and the mill was reduced from three shifts per day to two shifts per day. In December, however, the mill was again operated on all three shifts, mainly in order to make more efficient use of the company's

hydroelectric power and to conserve fuel oil.

Construction work.—The only construction work of importance during the year was that done in connection with a plan for the beneficiation of chrome ore in our mill. This work consisted of building conveyors, aerial tramway, bins, etc.

Labor.—All during the year there was a great shortage of both skilled and unskilled labor in the various departments. The labor turn-over was high, and the actual loss of employees was great. The number of employees at the beginning of the year was 866 as against 478 at the end of the year. The average labor turn-over for the year was over 100 percent.

In May 1942, wage increases amounting to about 12 percent were incorporated

into the agreement with the Juneau Mine & Mill Workers Union.

The average wage per day in 1942 was \$7.67 as against \$7.17 in 1941.

The overall cost per man per day was \$11.93 in 1942, as compared to \$11.14 in 1941.

### Gold content of ore from Alaska Juneau mine, 1938-42, and total, 1893-1942

			Gold (ounce)					
Year		ll from mine ns)		ry per ton milled	Losses per ton of tailings		Content of rock	
	Ore fine- milled	Coarse tailings rejected	In bul- lion	In galena concen- trates	Fine	Coarse	from mine to mill	
1938. 1939. 1940. 1941. 1942.	2, 478, 928 2, 377, 718 2, 308, 397 2, 211, 211 1, 624, 601	2, 184, 952 2, 270, 342 2, 431, 393 2, 143, 559 1, 140, 589	0. 0515 . 0454 . 0442 . 0451 . 0392	0.0081 .0088 .0089 .0092 .0071	0.0090 .0083 .0081 .0078 .0079	0.0071 0066 .0065 .0063 .0064	0, 0398 . 0352 . 0331 . 0347 . 0345	
Total and average, 1893-1942	46, 052, 845	40, 572, 603	. 0503	.0112	. 0118	.0084	.0429	

### Gold, silver, and lead recoveries from Alaska Juneau mine, 1893-1942

	G	old	Silv	ver	L	m-r-11	
Year	Fine ounces	Value	Fine ounces	Value	Pounds	Value	Total value recovered
1893-1913 1914-37 1938 1939 1940 1941	34, 239. 49 2, 204, 495. 44 148, 103. 14 129, 011. 74 122, 469. 96 120, 501. 24 75, 537. 00	54, 112, 836. 84 5, 183, 542. 98 4, 515, 410. 28 4, 286, 448. 37 4, 217, 897. 67	1, 412, 388. 41 121, 473. 25 111, 494. 24 100, 633. 39 95, 776. 56	78, 999. 04 75, 165. 90 71, 154. 36 67, 753. 89	2, 152, 714 2, 040, 280 1, 666, 016 1, 464, 956	104, 961. 22 89, 568. 57 85, 268. 93	5, 364, 487. 82 4, 695, 537. 40 4, 447, 171. 30
Total	2, 834, 358. 01	75, 667, 662. 06	1, 904, 064. 06	1, 183, 100. 18	39, 711, 231	2, 183, 200. 20	79, 033, 962. 44

<sup>&</sup>lt;sup>1</sup> Lost in tailings.

## Summary of production and operating costs, Alaska Juneau mine, 1914-42, inclusive

		inclus	rve					
	2, 765, 190	tons	4,354,770	tons	86,118,194	86,118,194 tons		
	1942	Per ton trammed	1941	Per ton trammed	1914–42	Per ton trammed		
Production (gross recovered gold, silver, and lead								
values): Bullion Concentrates	\$2, 242, 104. 03 507, 014. 16	\$0.811 .183	\$3, 509, 421. 76 861, 498. 73	\$0.806 .198	\$62, 337, 260. 39 15, 988, 971. 90	\$0.724 .186		
	2, 749, 118. 19	.994	4, 370, 920. 49	1.004	78, 326, 232. 29	. 910		
Costs: Mining	1, 095, 681. 58 791, 041. 94 167, 492. 84	. 396 . 286 . 061	1, 649, 946. 97 1, 005, 054. 65 265, 220. 42	. 379 . 231 . 061	26, 269, 453, 47 20, 972, 055, 47 4, 170, 038, 01	.305 .244 .048		
pay-roll taxes	139, 947. 19	. 051	220, 706. 62	. 051	1, 867, 546. 20	. 022		
Total Juneau operat- ing and marketing costs	2, 194, 163. 55 56, 392. 04	. 794 . 020	3, 140, 928. 66 77, 531. 84	.722	53, 279, 093. 15 3, 595, 047. 66	. 619 . 042		
Total operating costs and expenses	2, 250, 555. 59	.814	3, 218, 460. 50	.740	56, 874, 140. 81	. 661		
Juneau operating profit	554, 954. 64	. 200	1, 229, 991. 83	. 282	25, 047, 139. 14	. 291		
Net operating profitOther revenue (interest, etc.)_	498, 562. 60 75, 738. 81	.180	1, 152, 459, 99 50, 504, 47	. 264	21, 452, 091. 48 795, 391. 19	. 249		
Profit before depreciation, depletion, and income taxes	574, 301. 41		1, 202, 964. 46		22, 247, 482. 67			

The Hirst-Chichagof Mining Co. on Chichagof Island, 65 miles northwest of Sitka, operated its mine and 35-ton amalgamation-flotation mill continuously until closed on October 15 by the Gold Mining Limitation Order. The mill treated 3,584 tons of gold-silver ore, which yielded bullion containing 3,716 fine ounces of gold and 809 fine ounces of silver, and 110 tons of gold-silver concentrates containing 726 ounces of gold, 331 ounces of silver, and a minor amount of copper. Bullion produced was sent direct to the Seattle Assay Office, and the concentrates were shipped to the Tacoma (Wash.) smelter.

The Chichagof Mining Co. at Klag Bay on Chichagof Island shipped gold-silver concentrates and gold bullion recovered from milling operations conducted in 1941. The company did not operate the

mine or mill in 1942.

The output from other lode mines in the region was small and included production from the Williams mine in the Admiralty Island district; the Leroy and Rainbow lodes in the Juneau district; and the Gold Standard, Lucky Jack, Jessie, Dawson, and N & T mines in the Ketchikan district.

一日の日の日本の大学の一の一種はいった。

The Riverside tungsten mine in the Hyder district, owned and operated by J. H. Scott, shipped lead-silver-gold concentrates to the Bunker Hill & Sullivan smelter at Kellogg, Idaho. Tungsten concentrates stock-piled for a number of years because of the Jones Act of 1920 requiring shipments of concentrates to be made in American vessels are now being sent to the United States on Canadian boats owing to a recent Department of Commerce ruling.

Sluicing in the Juneau district in 1942 recovered small amounts of

placer gold.

Yukon River Basin region.—The Yukon River Basin region includes the following mining districts: Bonnifield-Nenana, Chandalar, Chisana, Circle, Delta River, Eagle, Fairbanks, Fortymile, Goodpaster, Hot Springs, Hughes, Iditarod, Innoko, Kantishna, Koyukuk, Marshall, Rampart, Ruby, Tolovana, and Yukon Flats. The region yielded 75 percent of the total output from connected-bucket dredges in Alaska during 1942; it again ranked third in gold recovered from lode mines.

Fifteen floating connected-bucket dredges were operating in the

region in 1942 compared with 22 in 1941.

The United States Smelting, Refining & Mining Co., operating seven floating connected-bucket dredges in the Fairbanks district, was much the largest producer of gold and silver in the Yukon River Basin region. The company operated two 10-cubic foot Bethlehem dredges (with 111 and 93 buckets, respectively), one 10-cubic foot Yuba dredge (with 106 buckets), one 3-cubic foot Yuba dredge (with 68 buckets), and three 6-cubic foot Bethlehem dredges (with 78, 78, and 68 buckets, respectively); all the dredges were electrically operated. Other equipment used (chiefly for removing overburden) included 315 Joshua Hendy hydraulic giants, one 8- to 12-cubic yard electric-powered Bucyrus 10-W dragline, and one oil-burning caterpillar bulldozer. Of the dredges operated in 1942, two were on Cleary Creek, two on Goldstream Creek, and one each on Cripple, Ester, and Pedro Creeks.

The Thirty-Seventh Annual Report of the United States Smelting, Refining & Mining Co., for the year ended December 31, 1942 (dated

March 23, 1943), says—

At the Alaska gold properties favorable development continued but the operations were shut down by Government order in the fall of 1942. Maintenance crews are keeping the dredges and plants in repair and in readiness for resumption of operations when that becomes possible. Some of the buildings and equipment have been leased to the Government and revenues will help to defray some of the shut-down expenses.

In the Circle district three dredges were again active in 1942. Alluvial Golds, Inc., operated its W. W. Johnson Co. dredge (with 72 4-cubic foot buckets) on Woodchopper Creek from May 27 to October 12. Gold Placers, Inc., operated a similar type of dredge equipped with 60 4-cubic foot buckets on Coal Creek from June 1 to October 13. The C. J. Berry Dredging Co. operated its steam-powered dredge (with 58 3-cubic foot buckets) and handled about 239,800 cubic yards of gravel.

In the Fairbanks district the Brinker-Johnson Co. operated its W. W. Johnson dredge (with 78 4½-cubic foot buckets) on Caribou

Creek from May 11 to October 4, 1942.

The North American Dredging Co. operated its Washington Iron Works dredge (with 70 3½-cubic foot buckets) on Otter Creek from June 1 to October 29. The J. E. Riley Investment Co. also operated a dredge on Otter Creek.

Two dredges were active in the Innoko district in 1942; the Ganes Mining Co. and Moss & Larson Mining Co. operated one each on

Ganes Creek.

All types of placer operations—other than floating connected-bucket dredges—were to be found throughout the Yukon River Basin region in 1942.

The largest producers of placer gold in the Bonnifield-Nenana district in 1942 were Dan Cole and the Gold King mine, both bulldozer

and hydraulic operations.

Among the larger producers in the Circle district using hydraulic giants and bulldozers or draglines with screening and sluicing plants were: The Berry Holding Co., John Frasca & Co., Half Dollar Mining.

Co., Switch Creek Mining Co., and Deadwood Mining Co.

In the Fairbanks district Helmer Johnson handled approximately 23,000 cubic yards of gravel with two hydraulic giants and a bulldozer at his placer on upper Cleary Creek. The Wolf Creek Mining Co. operated its dragline and washing plant on Wolf Creek and continued to be an important producer of placer gold. The Faith Creek Mining Co. on Faith Creek and the Fish Creek Mining Co. on upper Fish Creek recovered placer gold by hydraulicking, bulldozing, and sluicing. Other important producers in the Fairbanks district included the Alder Creek Mining Co., Brown & Reeves, A. A. Zimmerman, and Fred Parker.

The Wade Creek Dredging Co. confined its operations in 1942 to hydraulicking and bulldozing gravels at its claims on Uhler and Jack

Wade Creeks from May 1 to September 12.

Larger placer operators in the Hot Springs district were the Cleary Hill Mines Co., operating six hydraulic giants, one dragline, and two bulldozers on Sullivan and Eureka Creeks; J. R. Frank & Co., hydraulicking on Pioneer Creek; and Gold Mines, Ltd., operating a bulldozer and dragline on American Creek.

In the Iditarod district the Awe Mining Co., Granite Mining Co., Hatten, Bauquier & Turner, Peter Miscovich & Sons, Moore Creek Mining Co., Turner & Remington, and Uotila & Ogriz all operated during the 1942 season, using draglines, bulldozers, and hydraulics.

Hard & Uotila operated their hydraulic, bulldozer, and dragline equipment from April to October on Beaver and Ophir Creeks. Degnan & Rosander and the Cripple Creek Mining Co. operated similar equipment on Little Creek and Cripple Creek, respectively. Other large placer operators were McFarland & Hartley, S. R. Paulson, and Savage & Matheson.

On Caribou Creek in the Kantishna district Caribou Mines handled 125,925 cubic yards of gravel from June 15 to September 28, using a 1%-cubic yard dragline, washing plant, and stacker mounted on

crawlers.

The principal producer of gold in the Koyukuk district in 1942 again was Repo & Schwaesdall, operating hydraulic giants, bulldozers,

and a dragline on Myrtle Creek.

The Yukon Mining Co. did sluicing on bedrock from June 1 to September 15 on Buster and Windy Creeks in the Marshall district. Johnston & Ostnes and the Willow Creek Mining Co. worked gravels along Willow Creek with hydraulics, bulldozers, and draglines.

Other large producers among these types of placer operations in the Yukon River Basin region in 1942 were the Long Creek Mining Co. and the Midnight Mines, Developing & Operating Co., in the Ruby district, and the Amy Creek Mining Co., A. S. Warwick, and Parker & Son in the Tolovana district.

Lode mining in the Yukon River Basin region produced 14,478 fine ounces of gold and 3,441 fine ounces of silver in 1942 compared with

16,763 ounces of gold and 8,114 ounces of silver in 1941.

The leading producer of lode gold in the region in 1942 was Cleary Hill Mines, Inc., operating the Cleary Hill mine and amalgamation-flotation mill in the Fairbanks district 27 miles northeast of Fairbanks. The United States Smelting, Refining & Mining Co. operated its McCarty mine on Fairbanks Creek until October 15; the mine is equipped with a 10-ton amalgamation mill. The Hi Yu Mining Co. continued small-scale operations at its Hi Yu mine and 50-ton amalgamation mill on Fairbanks Creek until July, when the property was closed because of inadequate labor. Additional production of lode gold in the Fairbanks district in 1942 came from the Clipper, Rambone, Lookout, Oregon, and Wyoming claims.

In the Kantishna district the Red Top Mining Co. operated its

In the Kantishna district the Red Top Mining Co. operated its Banjo mine and 50-ton jig-, table-, and flotation-concentration mill until September, when a shortage of labor forced operations to cease.

### GOLD, SILVER, COPPER, LEAD, AND ZINC IN ARIZONA

(MINE REPORT)

By G. E. WOODWARD AND PAUL LUFF

#### SUMMARY OUTLINE

	Page		Page
Summary	231	Mining industry	237
Calculation of value of metal production			238
Mine production by counties	236	Metallurgic industry	238
		Review by counties and districts	243

### SUMMARY

The total value of the output of recoverable metals from mines in Arizona was \$114,525,600 in 1942 compared with \$97,638,310 in 1941—an increase of 17 percent (see fig. 1); it was the greatest value since 1929, when the total was \$155,567,133. Both the quantity and value of copper and zinc increased substantially in 1942; the quantity of lead decreased, but the value increased owing to the higher average price of the metal. The total value of the copper was \$95,199,654—a 24-percent gain over 1941; lead, \$1,979,448—an 11-percent gain; and zinc, \$3,445,092—a 39-percent gain. The value of the gold was \$8,877,785—a 20-percent loss; and silver, \$5,023,621—a 6-percent loss. The gold production represented 8 percent of the State total value, silver 4 percent, copper 83 percent, lead 2 percent, and zinc 3 percent. The value of the metals recovered from copper ore was \$103,195,449 in 1942, or 90 percent of the State total. The output of copper was greater in 1942 than in any year except 1929, when it was 830,628,411 pounds, and the output of zinc exceeded the record output of 1941.

Production of copper, lead, and zinc (especially copper) in Arizona in 1942 was affected by several factors: Premium prices for copper, lead, and zinc; labor shortage; difficulty in obtaining sufficient supplies; disputes on rates of pay; and inexperience and inefficiency of employee replacements. The Metals Reserve Co. announced that, effective February 1, 1942, premiums of 5 cents a pound for copper and 2% cents a pound for both lead and zinc would be paid for these metals produced in excess of certain fixed basic quotas. Each mine has its basic quota fixed according to 1941 production. Also, effective December 1, 1942, the Metals Reserve Co. announced that it would pay an additional premium of 2% cents a pound for lead and two additional premiums of 2% cents a pound for zinc for over-quota metal production. Special contracts were negotiated during the last quarter of the year with Metals Reserve Co., which provided for the mining of marginal or low-grade copper ores from certain areas of

some of the large Arizona copper producers.

The state of the s

A labor shortage began in April at the mines, mills, and smelters in Arizona, resulting from men leaving to take jobs on Government construction projects and in war industries where abnormally high wages were paid. This shortage became so acute during the summer that the output of ore from some of the mines was curtailed as much as 50 percent. The seriousness of the condition was recognized by the War Department, which in October furloughed about 1,100 soldiers for service in Arizona mines. This action tended to relieve the shortage but did not insure an adequate labor supply. The labor shortage at the Morenci open pit was partly relieved by the employment of a number of Navajo Indians.

The Government gold-mine closing order affected some of the gold producers in Arizona, but a majority of them had shut down several

months before the order was issued.

All tonnage figures are short tons and "dry weight"; that is, they do not include moisture.

The value of metal production herein reported has been calculated at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zinc 4
1938 1939 1940 1941 1942	Per fine ounce \$35, 00 35, 00 35, 00 35, 00 35, 00	Per fine ounce  5 \$0.646+ 6.678+ 7.711+ 7.711+ 7.711+	\$0.098 .104	Per pound \$0.046 .047 .050 .057	Per pound \$0.048 .052 .063 .075

1 Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from Jan. 18, 1837, to Jan. 31, 1934, was \$20.67+(\$20.671835) per fine ounce.

2 Treasury buying price for newly mined silver.

2 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.

4 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.

5 \$0.67878787.

7 \$0.71111111.

Mine production of gold, silver, copper, lead, and zinc in Arizona, 1938-42, and total, 1860-1942, in terms of recovered metals

Year	Mines produc- ing		Ore (short tons)	Gold (lode a	and placer)	Silver (lode and placer)		
	Lode	Placer	tons)	Fine ounces	Value	Fine ounces	Value	
1938 1939 1940 1941	885 976 1, 024 805 515	329 142 276 184 163	14, 203, 164 18, 793, 260 21, 572, 175 25, 491, 794 33, 920, 731	305, 043 316, 453 294, 807 315, 392 253, 651	\$10, 676, 505 11, 075, 855 10, 318, 245 11, 038, 720 8, 877, 785	7, 479, 153 7, 824, 004 7, 075, 215 7, 498, 260 7, 064, 467	\$4, 835, 008 5, 310, 839 5, 031, 264 5, 332, 096 5, 023, 621	
1860-1942			(1)	10, 427, 940	252, 473, 055	275, 752, 505	204, 905, 390	

<sup>1</sup> Figures not available.

Mine production of gold, silver, copper, lead, and zinc in Arizona, 1938-42, and total, 1860-1942, in terms of recovered metals—Continued

	Co	pper	Le	ead	Z	Total value	
Year	Pounds	Value	Pounds	Value	Pounds	Value	Total value
1938 1939 1940 1941 1942	421, 594, 000 524, 224, 000 562, 338, 000 652, 634, 000 786, 774, 000	\$41, 316, 212 54, 519, 296 63, 544, 194 77, 010, 812 95, 199, 654	21, 142, 000 21, 542, 000 26, 532, 000 31, 276, 000 29, 544, 000	\$972, 532 1, 012, 474 1, 326, 600 1, 782, 732 1, 979, 448	11, 628, 000 13, 422, 000 30, 912, 000 32, 986, 000 37, 044, 000	\$558, 144 697, 944 1, 947, 456 2, 473, 950 3, 445, 092	\$58, 358, 401 72, 616, 408 82, 167, 759 97, 638, 310 114, 525, 600
1860-1942	2 9, 840, 182	2, 936, 454, 870	2 296, 826	34, 479, 098	2 144, 825	22, 587, 893	3, 450, 900, 306

Short tons.

Gold and silver produced at placer mines in Arizona, 1938-42, in fine ounces, in terms of recovered metals

						Dre	dges			
Year	Sluici	ng 1	Drift n	Dry-land Dragline floating 2		Total				
	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver
1938 1939 1940 1941 1942	1, 624 1, 919 1, 625 976 885	213 227 207 125 176	328 1,850 646 77	35 125 41 5	(3) (2) 1, 186 824 35	(3) (8) 464 717 5	3 3, 033 3 2, 640 2, 784 10, 054 1, 916	3 380 3 339 396 1, 358 217	4, 985 6, 409 6, 241 11, 931 2, 836	628 691 1, 108 2, 205 398

3 Figures for dragline floating dredges include those for dry-land dredges.

Gold.—The output of recoverable gold in Arizona in 1942 was 253,651 fine ounces—a decrease of nearly 20 percent from 1941. Gold from siliceous ores (chiefly dry and siliceous gold ore) declined more than 34 percent and that from zinc-lead ore 38 percent; gold from copper ore increased only 2 percent. Gold from placers decreased from 11,931 to 2,836 ounces; half of the total placer gold in 1942 was recovered by dragline dredging at properties on Big Bug Creek in Yavapai County. The Copper Queen (Bisbee) branch of the Phelps Dodge Corporation continued to be the leading gold producer in Arizona; it was followed by the New Cornelia mine in Pima County, the Mammoth-St. Anthony Limited property in Pinal County, the United Verde mine in Yavapai County, the Goldroad mine (United States Smelting, Refining & Mining Co.) in Mohave County, and the Magma mine in Pinal County; these six properties produced nearly 72 percent of the State total output. Copper ore yielded 57 percent of the State total gold, siliceous ores 37 percent, and zinc-lead ore 3 percent. The chief gold-producing districts in Arizona were the Warren, Ajo, San Francisco, Verde, Old Hat, Weaver (Yavapai County), Pioneer (Superior), and Big Bug.

¹ Includes placer sands treated by dry concentration plants.
² A floating washing plant supplied with gravel by a dragline excavator is called a "dragline dredge"; a stationary or movable washing plant supplied with gravel by any type of power excavator is called a "dry-land dredge."




FIGURE 1.—Value of mine production of gold, silver, and copper and total value of gold, silver, copper, lead, and zinc in Arizona, 1870-1942. The value of lead and zinc has been less than \$2,000,000 annually, except in a few years.

Silver.—The output of recoverable silver in Arizona in 1942 was 7,064,467 fine ounces—a decrease of 6 percent from 1941. The chief decreases were 270,508 ounces in silver from siliceous ores, 85,554 ounces from zinc-lead ore, 32,237 ounces from zinc ore and zinc-copper ore, and 29,516 ounces from lead ore. Copper ore yielded 71 percent of the State total silver, siliceous ores 13 percent, zinc-lead ore 12 percent, zinc ore nearly 3 percent, and lead ore 1 percent. Phelps Dodge Corporation continued to be the chief silver producer in Arizona, and its output was 4 percent greater than in 1941; its four properties (Copper Queen, Morenci, New Cornelia, and United Verde) produced 50 percent of the State gold output, 60 percent of the silver, and 56 percent of the copper. Other large silver producers in Arizona in 1942 were the Magma, Trench-Flux, Iron King, and Shattuck Denn properties. The chief silver-producing districts were the Warren (Bisbee), Verde (Jerome), Pioneer (Superior), Ajo, Harshaw, and Big Bug; 57 percent of the State total silver came from the Warren and Verde districts.

Copper.—Arizona has been the largest producer of copper in the United States since 1907 except in 1909, when Montana held first The output of recoverable copper in Arizona in 1942 was 786,774,000 pounds—an increase of more than 20 percent over 1941 and larger than in any year except 1929, when it was 830,628,411 pounds. The Globe-Miami district, with a production of 188,529,000 net pounds of copper, continued to be the leading copper-producing area in Arizona; it was followed by the Ajo district with 133,293,800 pounds, Copper Mountain (Morenci) with 120,711,000 pounds, Warren (Bisbee) with 106,555,000 pounds, Mineral Creek (Ray) with 100,724,000 pounds, Verde with 87,874,000 pounds, and Pioneer (Superior) with 41,402,800 pounds. These seven districts contributed 99 percent of the State total copper. Copper ore and its products yielded 781,457,631 pounds of copper, as follows: 26,703,329 tons of copper ore treated by concentration yielded 63 percent; 1,954,374 tons of copper ore shipped crude to smelters, 21 percent; and 4,199,268 tons of copper ore leached and 26,781 tons of cement copper (from mine-water precipitates and underground leaching operations), 16 percent. The New Cornelia property continued to be the largest copper producer in Arizona; it was followed in order by the Morenci branch of the Phelps Dodge Corporation, Inspiration, Ray (Nevada Consolidated Copper Corporation), Copper Queen, United Verde, Miami, and Magma properties.

Lead and zinc.—The output of recoverable lead in Arizona in 1942 was 29,544,000 pounds—a decrease of more than 5 percent from the record output of 1941; the output of recoverable zinc was 37,044,000 pounds—the largest in any year in the history of the State and an increase of 12 percent over the record output of 1941. About 47 percent of the State total lead and 36 percent of the zinc came from Santa Cruz County, 13 percent of the lead and 24 percent of the zinc from Pinal County, and 11 percent of the lead and 12 percent of the zinc from Mohave County; most of the remainder of the lead and zinc came from Cochise and Yavapai Counties. About 75 percent of the total lead and more than 72 percent of the total zinc came from zinclead ore; nearly all the rest of the lead came from lead ore, siliceous ores, zinc ore, and copper ore; and nearly all the rest of the zinc came from zinc ore. The Trench-Flux group of the American Smelting & Refining Co. near Patagonia in Santa Cruz County was by far the largest producer of lead in the State and the largest producer of zinc; other large producers of lead were the Mammoth-St. Anthony Limited property at Tiger, Tennessee mine at Chloride, Iron King mine at Humboldt, Shattuck Denn mine at Bisbee, and Duquesne property near Patagonia; and other large producers of zinc were the Magma, Iron King, Duquesne, Tennessee, Shattuck Denn, Davenport

and Mammoth-St. Anthony Limited properties.

### MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in Arizona in 1942, by counties, in terms of recovered metals

County		produc- ng	Gold (lode a	and placer)	Silver (lode and placer)		
	Lode	Placer	Fine ounces	Value	Fine ounces	Value	
Cochise Coconino Glia Graham Greenlee Maricopa Mohave Pima Pinal Santa Cruz Yavapai Yuma	31 5 32 6 7 40 97 37 34 33 149 44	1 4 8 9 7 1 81 52	59, 332 15 2, 130 22 5, 707 2, 932 36, 246 45, 603 38, 500 5116 61, 430 1, 218	\$2,076,620 525 74,550 199,745 102,620 1,268,610 1,596,105 1,347,500 18,060 2,150,050 42,630	2, 539, 779 102, 912 3, 877 336, 202 8, 969 193, 109 514, 381 839, 506 514, 845 1, 960, 529 49, 628	\$1, 806, 065 517 73, 184 2, 757 239, 077 6, 378 137, 322 365, 782 596, 982 366, 112 1, 394, 154 35, 291	
Total, 1941	515 805	163 184	253, 651 315, 392	8, 877, 785 11, 038, 720	7, 064, 467 7, 498, 260	5, 023, 621 5, 332, 096	

	Cor	per	Le	ad	Zi	ne	(Date) l	
County	Pounds	Value	Pounds	Value	Pounds	Value	Total value	
Cochise Coconino	107, 002, 000 172, 000	\$12, 947, 242 20, 812	2, 979, 000 1, 000	\$199, 593 67	3, 534, 000	\$328, 662	\$17, 358, 182 21, 921	
Gila Graham	190, 257, 000 8, 000	23, 021, 097 968	873, 000 305, 400	58, 491 20, 462	695, 000	64, 635	23, 291, 957 24, 957	
Greenlee Maricopa Mohave	120, 711, 000 178, 200 365, 200	14, 606, 031 21, 562 44, 189	11, 300 507, 300 3, 318, 300	757 33, 989 222, 326	4, 487, 700	417, 356	15, 045, 610 164, 549 2, 089, 803	
Pima Pinal	134, 517, 900 142, 348, 000	16, 276, 666 17, 224, 108	236, 000 3, 980, 600	15, 812 266, 700	226, 300 8, 925, 000	21, 046 830, 025	18, 275, 411 20, 265, 315	
Santa Cruz Yavapai Yuma	1, 201, 000 89, 881, 700 132, 000	145, 321 10, 875, 686 15, 972	13, 853, 000 2, 624, 300 854, 800	928, 151 175, 828 57, 272	13, 506, 000 5, 670, 000	1, 256, 058 527, 310	2, 713, 702 15, 123, 028 151, 165	
Total 1041	786, 774, 000	95, 199, 654	29, 544, 000	1, 979, 448	37, 044, 000	3, 445, 092	114, 525, 600	
Total, 1941	652, 634, 000	77, 010, 812	31, 276, 000	1, 782, 732	32, 986, 000	2, 473, 950	97, 638, 310	

Gold and silver produced at lode mines in Arizona in 1942, by counties, in terms of recovered metals

County	Ore sold or treated (short tons)	Gold (fine ounces)	Silver (fine ounces)
Cochise. Coconino. Gila. Graham. Greenlee. Maricopa. Mohave. Pima Pinal Santa Cruz. Yavapai	1, 225, 285 1, 619 11, 019, 394 1, 304 7, 715, 637 41, 004 269, 499 8, 344, 994 3, 590, 696 111, 198 1, 585, 322 14, 779	59, 331 15 2, 130 22 5, 697 2, 921 36, 192 45, 597 38, 500 515 58, 890 1, 005	2, 539, 779 727 102, 915 3, 877 336, 202 8, 969 193, 102 514, 381 839, 506 514, 845 1, 960, 252 49, 514
Total, 1941	33, 920, 731 25, 491, 794	250, 815 303, 461	7, 064, 069 7, 496, 055

Gold and silver produced at placer mines in Arizona in 1942, by counties, in fine ounces, in terms of recovered metals

						Dre	edges			
County	Sluic	ing 1	Drift r	Drift mining Dry-land : Dragli in		Dragline ing	float-	Tot	al	
	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver
Cochise	1 10								1 10	
Maricopa Mohave Pima Santa Cruz	11 54 6	7							11 54 6	7
Yavapai Yuma	589 213	55 114			35	5	1, 916	217	2, 540 213	277 114
Total, 1941	885 976	176 125	77	5	35 824	717	1, 916 10, 054	217 1, 358	2, 836 11, 931	398 2, 205

<sup>&</sup>lt;sup>1</sup> Includes placer sands treated by dry concentration plants.
<sup>2</sup> A floating washing plant supplied with gravel by a dragline excavator is called a "dragline dredge"; a stationary or movable washing plant supplied with gravel by any type of power excavator is called a "dryland dredge."

### MINING INDUSTRY

In spite of a serious labor shortage during the summer months in the large copper-producing and zinc-lead districts in Arizona, more ore was mined in 1942 than in any year in the history of the State. The total output (33,920,731 tons) exceeded the peak year 1929 by 8,059,959 tons. The output of copper ore was 32,856,971 tons—a 36-percent gain over 1941; zinc-lead ore, 265,780 tons—a 2-percent gain; lead ore, 25,898 tons—a 41-percent gain; and zinc ore and zinc-copper ore, 113,667 tons—a 37-percent gain. Most of the gold mines in Arizona shut down before July 1, and the output of siliceous ores (chiefly gold ore) was 657,942 tons—a 33-percent loss from 1941. A total of 32,717,333 tons (96 percent of the State total ore output) was copper ore mined in the Globe-Miami, Ajo, Copper Mountain (Morenci), Mineral Creek (Ray), Verde (Jerome), Warren (Bisbee), and Pioneer (Superior) districts; most of the zinc-lead ore was mined in the Big Bug, Harshaw, Wallapai (Chloride), Patagonia, Old Hat (Oracle), and Warren (Bisbee) districts. Placer mining declined considerably, owing to exhaustion of commercial dredging ground.

### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

Ore sold or treated in Arizona in 1942, with content in terms of recovered metals

Source	Mines produc- ing	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)
Dry and siliceous gold ore Dry and siliceous gold-silver ore Dry and siliceous silver ore	216 28 36	124,668	9, 691	379, 480	693, 839	56,071	
Copper ore Lead ore Zinc ore Zinc-copper ore Zinc-lead ore	1 278 125 113 9 4 2 18	32, 856, 971 25, 898 473 106, 400 7, 267	144, 764 2, 174 15 1, 152 10	4, 993, 551 101, 469 2, 397 198, 954 6, 377	2 781,457,631 85, 258 18, 733 2, 128, 230 356, 300	318, 900 4, 251, 345 34, 966 478, 000	9, 503, 100 679, 060
Total, lode mines Total, placers	1 515 163	33, 920, 731	250, 815 2, 836		2 786,774, 000	29, 544, 000	37, 044, 000
Total, 1941		33, 920, 731 25, 491, 794			<sup>2</sup> 786,774,000 <sup>3</sup> 652,634,000	29, 544, 000 31, 276, 000	37, 044, 000 32, 986, 000

A mine producing more than 1 class of ore is counted but once in arriving at total for all classes.
 Includes 129,292,755 pounds recovered from ore leached and mine-water precipitates.
 Includes 118,450,902 pounds recovered from ore leached and mine-water precipitates.

### METALLURGIC INDUSTRY

Of the 33,920,731 tons of ore produced in 1942 in Arizona, 27,102,358 tons (80 percent) were treated at concentration plants, 4,199,268 tons (12 percent) at a leaching plant, 543,681 tons (2 percent) at amalgamation, cyanidation, and cyanidation-concentration mills, and 2,075,424

tons (6 percent) were shipped crude to smelters.

Gold ore treated at amalgamation mills decreased from 7,517 tons in 1941 to 765 tons in 1942 and siliceous material treated at cyanidation and evanidation-concentration plants from 826,393 to 542,916 tons; 15 straight cyanidation plants treated 337,350 tons of material in 1942. The most important plants were those at the Goldroad, Gold Standard, Producers Mines, Inc., Congress, Octave, Mammoth-St. Anthony Limited, Alvarado, Yarnell, Vulture, Vivian, and Iron King properties. Nine companies reported cyaniding 386,332 tons of siliceous material and using 51,400 pounds of sodium cyanide, 666,265 pounds of Aero Brand calcium cyanide, 56,248 pounds of zinc dust, 2,000,000 pounds of lime, 1,277 pounds of Aerosol, and 8,800 pounds of caustic soda.

Ore treated at concentration plants in 1942 comprised chiefly 26,703,329 tons of copper ore, 265,505 tons of zinc-lead ore, 105,971 tons of zinc ore, and 12,121 tons of lead ore. Copper ore from the Miami property (5,922,250 tons) was treated by a combination of leaching and concentration, and copper ore from the Inspiration mine was treated by straight leaching and by leaching and concentration. The large copper-concentration plants at Ajo, Clarkdale, Hayden, Miami, Morenci, and Superior were operated at capacity in 1942, as well as the copper-leaching plants at Inspiration and Miami and the copper smelters at Clarkdale, Douglas, Hayden, Miami, Morenci, and Superior. The rated capacity of charge of the six copper smelters was as follows: Clarkdale 1,400,000 tons per year, Douglas 1,600,000,

Hayden 360,000, Miami 360,000, Morenci 450,000, and Superior (Magma) 210,000. In 1942 these plants treated copper material chiefly from one property, with the exception of the Douglas plant, which treated material from various properties in Arizona, New Mexico, and Mexico. The new 25,000-ton concentrator at the Morenci branch of the Phelps Dodge Corporation started running in January, and the new 1,200-ton-per-day copper smelter at Morenci began operating in April. The 20-ton smelter at Tiger is the only lead smelter in Arizona, and it operated exclusively on concentrates from the mill of Mammoth-St. Anthony Limited.

The following tables give details of the treatment of all ores pro-

duced in Arizona in 1942.

Mine production of metals in Arizona in 1942, by methods of recovery, in terms of recovered metals

Method of recovery	Material treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)
Ore amalgamated Ore, old tailings, and current tailings cyanided Concentrates smelted Ore smelted	765 539, 154 1, 322, 817 2, 075, 424	327 45, 713 105, 078 99, 697	146 103, 800 2, 668, 316 4, 291, 807	495, 590, 461 161, 890, 784	25, 760, 110 3, 783, 890	36, 734, 500 309, 500
Copper precipitates smelted Copper ore leached Placer	26, 781 2 4, 199, 268	2,836	398	1 41, 734, 764 87, 557, 991		
Total, 1941		253, 651 315, 392	7, 064, 467 7, 498, 260	786, 774, 000 652, 634, 000	29, 544, 000 31, 276, 000	37, 044, 000 32, 986, 000

<sup>&</sup>lt;sup>1</sup> Distributed as follows: Cochise County, 1,067,000 pounds; Gila County, 11,441,500 pounds; Greenlee County, 13,750,000 pounds; Pinal County, 14,749,964 pounds; Santa Cruz County, 1,600 pounds; and Yavapai County, 724,700 pounds.

<sup>2</sup> Treated by straight leaching at 1 plant in Gila County.

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in Arizona in 1942, by types of mills and by counties, in terms of recovered metals

#### AMALGAMATION MILLS

		Recovered	Recovered in bullion		Concentrates smelted and recovered metal						
County	Material treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Concentrates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)			
Cochise	2 210 207 105 225 16	12 9 187 9 107 3	3 4 99 7 32	3 2	13 4	23 17		610			
Total, 1941	765 7, 517	327 888	146 297	5 73	17 320	40 145	1, 200	610 1, 505			

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in Arizona in 1942, by types of mills and by counties, in terms of recovered metals—Continued

### CYANIDATION MILLS

		Recovered	in bullion	Concentrates smelted and recovered metal						
County	Material treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Concentrates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)		
Cochise	250	10	353							
Maricopa	35,085	1,582	1,358	351	720	300	865	1, 300		
Mohave	189, 843 1, 700	30, 778 307	39, 530 1, 298							
Pinal Yavapai	147, 483 168, 555	2,877 10,159	7, 121 54, 140	3, 292 470	22, 027 6, 141	21, 150 7, 421	11, 070 12, 426	2, 163, 000 69, 900		
Total, 1941	542, 916 826, 393	45, 713 77, 627	103, 800 182, 503	4, 113 5, 978	28, 888 37, 445	28, 871 41, 856	24, 361 34, 856	2, 234, 200 4, 455, 570		
G rand total:1942 1941		46, 040 78, 515	103, 946 182, 800	4, 118 6, 051	28, 905 37, 765	28, 911 42, 001	24, 361 36, 056	2, 234, 810 4, 457, 075		

Mine production of metals from concentrating mills in Arizona in 1942, by counties, in terms of recovered metals

		Concentrates smelted and recovered metal								
County	Material treated (short tons)	Concentrates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)			
Cochise	22, 132 6, 763, 756 7, 640, 890	5, 953 171, 133 267, 549	402 1, 894 4, 089	43, 030 86, 514 157, 971	505, 278 88, 560, 151 106, 100, 000	1, 285, 678 502, 700	3, 464, 000 683, 600			
Maricopa Mohave Pima	1, 300 73, 090 8, 338, 033	163 10, 390 227, 949	3, 265 45, 068	959 138, 967 499, 824	169, 215 134, 047, 982	143, 250 3, 235, 322	4, 487, 700			
Pinal Santa Cruz Yavapai Yuma	3, 352, 395 108, 443 791, 277 11, 042	302, 503 26, 062 306, 249 748	9, 054 229 12, 018 13	508, 622 477, 313 719, 883 6, 322	114, 889, 055 1, 169, 099 50, 124, 005 800	1, 765, 900 13, 630, 685 2, 161, 765 800, 000	8, 925, 000 13, 506, 000 5, 668, 200			
Total, 1941	27, 102, 358 19, 001, 720	1, 318, 699 1, 022, 801	76, 173 77, 209	2, 639, 405 2, 740, 172	495, 566, 100 378, 807, 603	23, 525, 300 22, 524, 350	36, 734, 500 32, 693, 800			

Gross metal content of concentrates produced from ores mined in Arizona in 1942, by classes of concentrates smelted

	Concen-	Gross metal content								
Class of concentrates	trates pro- duced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)				
Dry gold	560 1, 251, 630 25, 468 4, 793 37, 667 575 1, 454 670	1, 549 66, 122 32, 703 637 1, 182 8 55 2, 822	2, 268 1, 706, 798 626, 002 195, 440 129, 247 1, 000 3, 224 4, 337	3, 457 508, 491, 234 454, 094 438, 751 765, 241 42, 500 41, 793 5, 992	8, 214 513, 555 22, 366, 797 4, 086, 862 1, 708, 450 5, 000 391, 337 62, 342	3, 274, 011 2, 781, 199 973, 900 39, 321, 089 602, 000 1, 357, 24- 24, 630				
Total, 1941	1, 322, 817 1, 028, 852	105, 078 114, 974	2, 668, 316 2, 782, 173	510, 243, 062 392, 814, 679	29, 142, 557 29, 511, 821	48, 334, 06 43, 318, 94				

# Mine production of metals from Arizona concentrates shipped to smelters in 1942, in terms of recovered metals

### BY COUNTIES

	Concen- trates (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)	
Cochise Gila Greenlee	267, 549	402 1,894 4,089	43, 030 86, 514 157, 971	505, 278 88, 560, 151 106, 100, 000	. 1, 285, 678 502, 700	3, 464, 00 683, 60	
Maricopa Mohave Pima Pinal	514 10, 393 227, 949	861 3, 278 45, 068	1, 259 138, 990 499, 824	1, 380 169, 215 134, 047, 982	144, 550 3, 235, 932	4, 487, 70	
Santa Cruz Yavapai Yuma	305, 795 26, 064 306, 719 748	31, 081 233 18, 159 13	529, 772 477, 330 727, 304 6, 322	114, 900, 125 1, 169, 099 50, 136, 431 800	3, 928, 900 13, 630, 685 2, 231, 665 800, 000	8, 925, 00 13, 506, 00 5, 668, 20	
Гоtal, 1941	1, 322, 817 1, 028, 852	105, 078 114, 974	2, 668, 316 2, 782, 173	495, 590, 461 378, 843, 659	25, 760, 110 26, 981, 425	36, 734, 50 32, 693, 80	
	BY CLASS	ES OF C	ONCENTE	RATES		•	
Dry gold Jopper ⊥ead		1, 549 66, 122 32, 703	2, 268 1, 706, 798 626, 002	2, 761 494, 181, 808 361, 747	6, 700 64, 190 20, 560, 103		
ead-copper	4, 793 37, 667 575	637 1, 182 8	195, 440 129, 247 1, 000	359, 365 611, 889 34, 500	3, 712, 545 1, 109, 047 3, 300	35, 004, 41, 522, 360	
inc-leadron	1, 454 670	2,822	3, 224 4, 337	33, 643 4, 748	248, 192 56, 033	1, 207, 72	
	1, 322, 817	105, 078	2, 668, 316	495, 590, 461	25, 760, 110	36, 734, 500	

### Gross metal content of Arizona crude ore shipped to smelters in 1942, by classes of ore

	0		Gross metal content								
Class of ore	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)					
Dry and siliceous gold Dry and siliceous gold-silver Dry and siliceous silver	16, 607 56, 911 32, 944	9,157 7,994 961	33, 020 328, 208 410, 182	307, 018 714, 640 25, 517	37, 144 74, 457 17, 122						
CopperLead Lead-copper ZineZino-lead	1, 954, 374 13, 777 107 429 275	79, 420 2, 157 8	3, 425, 115 93, 581 1, 573	173, 003, 746 104, 243 9, 446	514, 546 3, 618, 216 28, 849 28, 400	279, 46					
Total, 1941	2, 075, 424 1, 870, 510	99,697 109,972	4, 291, 807 4, 531, 082	174, 164, 610 166, 596, 538	46, 763 4, 365, 497 4, 960, 747	383, 484 343, 601					

Mine production of metals from Arizona crude ore shipped to smelters in 1942, in terms of recovered metals

### BY COUNTIES

	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds	
Cochise	1, 202, 901	58, 907	2, 496, 393	105, 429, 722	1, 693, 322	70, 000	
CochiseCoconinoGila	1, 619 56, 370	15 236	727 16, 401	172,000 2,697,358	1, 000 370, 300 305, 400	11, 400	
GrahamGreenlee	1, 304 74, 747	1,608	3, 877 178, 231	8,000 861,000	11, 300		
Maricopa Mohave	4, 409 6, 359	469 1, 949	6, 348 14, 483	176, 820 195, 985	362, 750 82, 368	226, 300	
PimaPinal	5, 261 90, 818	222 4, 542	13, 259 302, 613	469, 918 12, 697, 911	236, 000 51, 700 222, 315	220, 300	
Santa Cruz Yavapai Yuma	2, 650 625, 265 3, 721	273 30, 465 989	37, 508 1, 178, 776 43, 191	30, 301 39, 020, 569 131, 200	392, 635 54, 800	1,800	
	2, 075, 424	99, 697 109, 972	4, 291, 807 4, 531, 082	161, 890, 784 155, 339, 439	3, 783, 890 4, 294, 575	309, 500 292, 200	
Total, 1941	1, 870, 510 BY	109, 972 CLASSE	4,531,082   S OF ORE	155, 339, 439	4, 294, 575	292, 20	
	16, 607	9, 157	33, 020	292, 503	24, 747		
Dry and siliceous gold		7 004		673 227	56 071 1	and the second second	
Dry and siliceous gold-silver	56, 911 32, 944	7, 994 961	328, 208 410, 182	673, 227 24, 434	56, 071 11, 252		
Dry and siliceous gold-silver Dry and siliceous silver Copper Cop	56, 911 32, 944 1, 954, 374 13, 777	7, 994 961 79, 420 2, 157	328, 208 410, 182 3, 425, 115 93, 581	24, 434 160, 808, 794 83, 948	11, 252 318, 900 3, 294, 754		
Dry and siliceous gold-silver Dry and siliceous silver Copper	56, 911 32, 944 1, 954, 374	7, 994 961 79, 420	328, 208 410, 182 3, 425, 115	24, 434 160, 808, 794	11, 252 318, 900		

### REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, lead, and zinc in Arizona in 1942, by counties and districts, in terms of recovered metals

County and district	Mine duo	s pro- cing	Ore sold or treated	Gold (fine ounces)			Silver (fine ounces)			Copper	Lead	Zine	Total
	Lode	Placer	(short tons)	Lode	Placer	Total	Lode	Placer	Total	(pounds)	(pounds)	(pounds)	value
Cochise County: California Cochise Dos Cabezas and Tevis Golden Rule (Dragoon) Hartford (Huachuea Mountains) Swisshelm Tombstone Turquoise	5 3 3 1 2 4 5	1	123 7, 395 512 78 74 2, 283 3, 674 970	1 17 138 24 3 52 354 50	1	1 17 138 24 4 52 354 50	3, 631 353 156 509 17, 415 29, 319 3, 652		609 3, 631 353 156 509 17, 415 29, 319 3, 652	1, 300 413, 000 7, 000 200 300 4, 600 17, 900 2, 700	14, 300 17, 300 4, 000 8, 000 25, 000 701, 300 399, 000 183, 300	70,000	\$1,583 107,040 6,196 1,511 2,213 61,748 62,138 23,465
Warren Coconino County: Francis. Jacob Canyon and Warm Springs. Navajo Reservation. Gila County:	3 1 3 1		1, 210, 176 31 1, 463 125	58, 692 15		15	2, 484, 135 14 661 52		14 661 52	2, 000 159, 000 11, 000	1,626,800	2,897,000	252 20, 301 1, 368
Banner and Dripping Springs. Globe-Miami. Green Valley. Mazatzal Mountain. Pioneer (Pinal Mountains). Summit.	8 16 2 1 4		44, 708 10, 974, 497 105 3 69 12	171 1,924 30 1 4		171 1,924 30 1 4	20, 260 81, 644 14		20, 260 81, 644 14	1,723,200 188,529,000 3,000 1,000 800	679, 300 193, 700	683,600 11,400	337, 987 22, 951, 445 1, 423 35 970 97
Graham County: Aravaipa. Lone Star Greenlee County: Ash Peak. Conner Mountain (Morenei)	5 1 2 4		1, 295 9 20, 756 7, 694, 849	778 4, 906		778 4, 906	3, 853 24 170, 519 165, 645		3, 853 24 170, 519	6,000 2,000			24, 698 259 148, 488 14, 896, 042
Copper Mountain (Morenci) Metcalf (Greenlee) San Francisco Maricopa County: Big Horn Blue Tanks		4 1 1	25	13	10 1 3	13 10 13 3	38		38		3, 700 300		730 350 475 105
Cave Creek and Camp Creek Ellsworth (Harqua Hala)! Estrella Mountain New River Osborn Pikes Peak (Morgan City)	6 1 1 5 2		250 4 25 1,927 1,624 20	24 55 99 20		24 55 99 20	322 14 737 2, 925 14		322 14 737 2, 925 14	300 161,600 11,800	313, 400		2, 696 36 850 22, 003 27, 971 710
Salt River Mountains	2		663	248		248	201		201	300	,		8,859

243

Mine production of gold, silver, copper, lead, and zinc in Arizona in 1942, by counties and districts, in terms of recovered metals—Continued

County and district	Mine duc	s pro- eing	Ore sold or treated	Go	ld (fine o	unces)	Silver	(fine oun	ces)	Copper (pounds)	Lead (pounds)	Zine (pounds)	Total value
Councy and about	Lode	Placer	(short tons)	Lode	Placer	Total	Lode	Placer	Total	(pounds)	(pounds)	(pounds)	Value
faricopa County—Continued.	2	6	9	14	7	21					200		\$748
San Domingo Sunflower	2	0	52	48	- 1	48	38		38		200		1,707
Vulture	12		35, 397	2, 273		2, 273	4.604		4, 604	2,900	193, 400		96, 138
Wickenburg	Ĩ		1,000	56		56	114		114				2,041
Winifred	î		7, 8	6		6							210
Iohave County:			_				100				4 4 5 222		
Bentley	1		36				104		104	17, 900	200		2, 253
Cedar Ridge	1		113				14		14	2,700			33
Cedar Valley	1		10.000	4		4	959		959	39, 100			5, 55
Chemehuevis		1			17	17		7	7				600
Cottonwood	1		2,030	165		165	682		682	58, 300			13, 314
Gold Basin	4	4	249	108	19	127	24		24	100			4, 462
Greenwood	2		11	2		2	14		14	100			92
Indian Secret (White Hills)	1		250	- 3		3	1, 156		1, 156				630
Lost Basin	<b></b>	4			18	18 22	83		83	100	1,800		965
Maynard and McConnico	2		125	22 65		65	502		502	100	400		2, 65
Minnesota	ō		171 259	328		328	689		689		2,700		12, 15
Music Mountain	13		2,976	498		498	720		720	106, 300	7,600		30, 84
Owens	10		2, 870	400		100	120		7	3, 900	000		47
Peacock San Francisco (Oatman, Goldroad, Kathe-	1		20							0,000			
rine, Vivian)	17		178, 859	28, 570		28, 570	30, 804	1.0	30, 804				1,021.85
Wallapai	36		70, 533	5, 406		5. 406	157, 112		157, 112	136, 800	3, 312, 600	4, 487, 700	956, 78
Weaver	6		3, 861	1.021		1,021	232		232				35, 900
ima County:	·		0,001	-,		_, -,			No. of the				
Aio	1	4	8, 324, 737	45.081	l	45, 081	489, 759		489, 759	133, 293, 800			18, 054, 65
Amole	Ž.		618	89		89	1,523		1, 523	3,200	78,600		9,85
Arivaca	6	3	79	57	2	59	239		239	300			2, 27
Baboquivari	i		1,700	307		307	1, 298		1, 298				11,66
Cababi (Comobabi)	5		85	9		9	149		149	2,700	2,600		92
Cerro Colorado	1		67	1		1	2, 589		2, 589	1, 200	1,700		2, 13
Empire	1		574	6		6	720		720	2,000	77,000	226, 300	27, 16
Greaterville		1			2	2							70
Helvetia (Rosemont)	3		4, 465	11		11	3, 631		3,631	449,000	3,000		57, 49
Old Hat 2	.3		12, 149	25		25 8	11,091		11,091	742,000			98, 54
Pima (Sierritas, Papago, Twin Buttes)	9		166	8			1,028		1,028 121	9, 700 4, 000	22,000		3, 659 95
Quijotoa	3	3	65		2	2	121			8, 000			3.83
Roskruge and Waterman	1		189	1		1 2	1,409		1, 409 824	2,000	10 100		2, 17
Silver Bell	1		100	2		2	824		824	2,000	19, 100		2, 17
inal County:		1					070		976	48,000	14, 300		7, 740
Bunker Hill	. 2		580 443	8 39		8	976 5, 362		5. 362 °	8, 200	14,000		6, 75

ColdMeldis	Cottonwood and Black Mountain	. 2	. 1	30	16	1	16	52		52	200	l		621
Hackberry	Colonwood and Diack Mountain	1			7		Ť	31		31				267
Mineral Creek   2   2,969,644   852   852   66,025   66,025   100,724,000   12,964,375	Trobbone	1					•					3, 400		243
Mitheral Hill.	TRUE DELTY	1 6			050		959				100 724 000	-,		
Old Hat 1.	Mineral Creek	2						1,025		1 025	200, 124, 000	28 800		
Ploneer (Superior)		6		1, 123								20,000	1 157 000	
Sand Gle Mountain	Old Hat 2	4						40,621						
Sand   Mountain	Pioneer (Superior)	7		455, 651	11, 130		11, 130	725, 137		725, 137	41, 402, 800	325,000	7, 768, 000	
Santa Cruz County:	Saddle Mountain	2		30	4		4	246		246	1, 200			460
Harshaw	Santa Cruz County	-		500										
Oro Blanco         10         1         1,811         200         1         270         28,149         28,149         9,800         12,000         31,477           Palmetto         1         1         7         7         816         8         31,374         38         38         18,659         138,659         886,300         1,800         29,800         65,587           Tyndall         7         816         8         8         4,185         4,185         7,200         187,000         29,300         19,381           Yavapai County:         2         37         1         1         353         318,659         138,659         187,000         187,000         29,300         19,381           Bear Canyon         1         450         15         15         11         111         30,000         19,381         19,381           Bear Canyon         1         17         15,510         7,586         1,584         9,822         316,807         114         316,000         1,000         2,000         1,000         1,000         2,000         1,000         3,000         1,000         3,000         1,000         3,000         1,000         3,000         1,000         3,000 </td <td>Horehow,</td> <td></td> <td></td> <td>77 152</td> <td>199</td> <td></td> <td>199</td> <td>343, 357</td> <td></td> <td>343, 357</td> <td>296, 000</td> <td>12, 264, 400</td> <td>9, 650, 000</td> <td>2,006,111</td>	Horehow,			77 152	199		199	343, 357		343, 357	296, 000	12, 264, 400	9, 650, 000	2,006,111
Palmetto	One Diemos	1 10										12,000		31, 457
Palmetto	Oro Dianco	10	1	1,011	200		2.0	20, 110		20, 110	0,000			
Patagonia	Pajarito	1 .1		Ł				140		140				
Tymodall	Palmetto	1 1		7							000 000		9 998 700	
Wrightson	Patagonia	8								138, 009				
Wrightson         2         37         1         1         363         303         1,700         7,000         1,008           Yavapal County:         2         450         15         15         111         111         39,900         5,432         1,008	Tyndall	7		816	8		8			4, 185			29,300	
Yavapal County:         Agus Fria.         2         450         15         15         111         111         39,900         5,432           Bear Canyon.         1         17         155,910         7,898         1,584         9,482         318,807         114         316,921         260,700         1,905,700         5,800,000         1,209,383           Black Canyon.         7         1         1,214         247         2 249         6,781         1,300         25,000         1,209,383           Black Canyon.         7         1         1,214         247         2 249         6,781         1,300         25,000         1,209,383           Black Rock         7         1,234         172         172         159         156         11,200         6,700         7,882           Bule Tank         1         3         43         16         9         25         17         76         153,900         25,000         115,309           Bullar Tank         1         3         43         16         9         25         17         76         153,500         17         9,425         118         118         118         10         11,400         10         11,400 <td>Wrightson</td> <td>2</td> <td></td> <td>37</td> <td>1</td> <td></td> <td>1</td> <td>353</td> <td></td> <td>353</td> <td>1,700</td> <td>7,700</td> <td></td> <td>1,008</td>	Wrightson	2		37	1		1	353		353	1,700	7,700		1,008
Agus Fris. 2 4 450 15 15 11 1 39,900	Vavanai County	l												
Bear Caryon		9		450	15.		15	111	1	111	39, 900	l		5, 432
Big Bug.	Don Common			24				7		7	1 300			162
Black Canyon	Dear Canyon	1		188 010	7 000	1 504	0 400	218 907	114	216 021		1 905 700	5 300 000	1 200 363
Black Hills	Big Bug	1 10				1,004	9, 402		114			25,000		
Black Rock   7		7	1	1, 214		2		0, 781		0, 701		20,000		
Blue Tank	Black Hills	. 3												
Bilte Tank	Black Rock	7			172						11,200	6,700		
Castle Creek   7	Blue Tank	1	3	43		9								
Castle Creek         7         96         7         7         111         111         3,300         17,400         1,839           Cherry Creek         8         288         150         150         114         1114         1114         3,300         17,400         1,839           Copper Basin         5         7         9,425         108         15         123         450         450         456,700         1,000         66,000         66,001           Copper Creek         1         1         60,66         841         841         20,513         20,613         1,107,700         128,600         128,000         198,574           Hassayampa         17         9         285         433         546         979         2,520         128         2,648         700         7,600         36,742           Humbug         1         3         6         7         15         22         21         21         400         38,742           Kirkland         1         47         43         7         7         7,882         7         7         21         1,510           Lynx Creek         3         20         5         33,883         3,		3		290			58							
Cherry Creek		7		96	7		7	111	1		3, 300	17,400		
Copper Basin         5         7         9,425         108         15         123         450         456,700         1,000         66,000         66,000         66,000         41           Copper Creek         1         1         60,066         841         541         20,513         20,513         1,107,700         128,600         128,600         198,574           Hassayampa         17         9         285         433         546         979         2,520         128         2,648         700         7,600         38,742           Humbug         1         3         6         7         15         22         21         21         400         812           Kirkland         1         47         43         43         7         7         882         7         812           Martinez         5         33,853         3,107         3,107         7,882         7,882         7,882         7,882         7,882         114,350         14,350         14,4350         14,650         2,740         19,049         23,700         133,600         121,000         132,518         14,000         1,000         3,055         14,650         2,740         19,049         23,	Charry Crook	Q			150		150	114		114	1	1		5, 331
Copper Creek.         1         4         4         841         20,513         20,513         1,107,700         128,600         128,000         198,574           Bureka.         12         60,666         841         841         20,513         20,513         1,107,700         128,600         128,000         198,574           Hassayampa         17         9         285         433         546         979         2,520         128         2,648         700         7,600         86,742           Humbug         1         3         6         7         15         22         21         21         400         812           Kirkland         1         47         43         87         87         14	Conner Desin	1 2	7			15	123	450		450	456 700	1.000	66,000	66, 091
Copper Creek         12         60,066         841         541         20,513         20,513         1,107,700         128,000         128,000         198,674           Hassayampa         17         9         285         433         546         979         2,520         128         2,048         700         7,600         128,000         36,742           Humbug         1         1         3         6         7         15         22         21         21         400         36,742           Kirkland         1         47         43         43         7         14         14         1         400         3,055           Martinez         5         33,853         3,107         87         87         7,882         7,882			1	0, 420	100	1	1	7		107		2,000	1 00,000	
Hassayampa		1 -1		00.000			041	00 512		00 519		100 600	128 000	
Humbug									100	20,010	1,107,700			
Rinkland							9/9		128		100	1,000		
Lynx Creek	Humbug	. 1	3	6		15	22	21		. 21		400		
Lynx Creek   13   33,853   3,107   3,107   7,882   14   1,84   .	Kirkland	. 1		.47	43			7		7				
Martinez         5         33,853         3,107         7,882         7,82         8         7,82         8         8         8         8         8         8<	Lynx Creek	1	13			87			14					
Peck         3         209         5         2,740         4,666         4,666         2,300         133,600         121,000         33,718           Pine Grove.         6         1         2,740         201         201         201         201         23,700         133,600         121,000         132,518           Pocket Creek.         1         10         2         201         201         7         585         7         7         585         7         7         585         675         1,700         4,800         6,189         6,189           Tip Top.         4         14         1         1         128         128         1,700         1,000         389           Verde.         6         1,242,183         28,429         28,429         1,532,108         1,532,108         87,874,000         12,717,288           Wagoner.         2         1         2,767         1,132         20         1,152         13,213         7         13,220         60,300         72,700         55,000         67,000           Walnut Grove.         12         15         70,620         13,445         56         13,801         13,410         7         13,417         7			1	33, 853	3, 107		3.107	7.882						
Pine Grove	Dools	.) =					. 5	4,666	1	4,666	2, 300	1		3, 771
Pocket Creek								19 049				133,600	121,000	132, 518
Silver Mountain				4,000	2,110	201	201	10,010	7	7	20,100	100,000	122,000	
Silver   Note   Silver   Sil			.) .			201	201	FOR	•	EOE		1 000		
Tip Top		. 4					1 2				7 700	1,000		
Turkey Creek 1 1 239 28, 429 1 239 28, 429 1, 532, 108 27, 574, 000 27, 700 55, 000 67, 003 Walnut Grove 1 2 1 5 70, 520 13, 245 56 13, 301 13, 410 7 13, 417 15, 300 84, 000		.  6			149		149					4, 300		0, 109
Türkey Creek 1 1 1, 242, 133 28, 429 20 1, 152 18, 220 1, 532, 108 87, 874, 000 4,000 212, 717, 268 140 Wagoner 2 2 1, 77 4 1 1, 52 182 20 1, 152 18, 220 60, 300 72, 700 55, 000 67, 003 Walnut Grove 2 1 15 70, 520 13, 245 56 13, 301 13, 410 7 13, 417 15, 300 84, 000 482, 555	Tip Top	. 4		14	1		1				1,700	1,000		
Verde         6         1,242,183         28,429         28,429         1,532,108         1,532,108         87,874,000         12,717,288           Wagoner         2         4         4         4         4         4         4         140         14	Turkey Creek	. 1	1	. 7	1		1					4,000		
Wagoner     2     2     2,767     1,132     20     1,152     13,213     7     13,220     60,300     72,700     55,000     67,003       Walnut Grove     2     1     7     4     1     5     7     13,410     7     13,417     15,300     84,000     84,000     482,555     82,555			1	1. 242. 133	28, 429		28, 429	1, 532, 108		1, 532, 108	87, 874, 000			12, 717, 268
Walker		.)	2	,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,	1	4	4				l			140
Walnut Grove		177	1 5	2 767	1 132		1 152	13 213	7	13, 220	60, 300	72, 700	55,000	67,003
Waintt Grove 12 15 70, 520 13, 245 56 13, 301 13, 410 7 13, 417 15, 300 84, 000 482, 555			1	2,101	1,102			20, 210		20, 220	700	.2,.00	23,000	
W 68 VET			1 1	70 500	12 045			12 410		19 417		84 000		
White Picacho 3 1,171 6 6   20,295 20,295   20,205   20,205   20,205   20,205   20,205		12	1.5		10, 240	90			1					
	White Picacho	. 3		1,171	6		', 0	20, 295	'	20, 295	900	201, 500	[	00, 445

See footnotes at end of table.

Mine production of gold, silver, copper, lead, and zinc in Arizona in 1942, by counties and districts, in terms of recovered metals—Continued

County and district	Mines pro- ducing Ore sold or treated		Gold	Gold (fine ounces)		Silver (fine ounces)			Copper	Lead	Zinc	Total	
	Lode	Placer	(short tons)	Lode	Placer	Total	Lode	Placer	Total	(pounds)	(pounds)	(pounds)	value
Yuma County: Castle Dome Cienega Dome (Gila City)	3 2	1 10	11,053 826	41 152	111	152 152 10	6, 954 59	107	7,061 59	800 28, 800	821, 400		\$65, 47 8, 84 35
Dome (Gila City) Ellsworth (Harqua Hala)¹ Kofa Laguna LaPaz	2	5 2 3	640 2	126 4	9	126 13 1	294		294	44,800	300		10,06 45 3
La Posa Middle Camp and La Cholla Muggins Mountains New Water	1	10 2	35	1	18 1	1 18 1	7		7	400			17 8 63 3 25
Plomosa. Santa Maria (Planet, Bill Williams) Trigo.	8 1	13 6	1, 923 293	673 1	51 7	724 1 7	42, 141 52	7	42, 148 52	10,000 47,200	33, 100		58,74 5,78 24
Total Arizona	515	163	33, 920, 731	250, 815	2, 836	253, 651	7, 064, 069	398	7, 064, 467	786, 774, 000	29, 544, 000	37, 044, 000	114, 525, 60

<sup>&</sup>lt;sup>1</sup> Ellsworth district lies in both Maricopa and Yuma Counties.
<sup>2</sup> Old Hat district lies in both Pima and Pinal Counties.

A CONTRACT OF THE PROPERTY OF

Comment on districts with small production has been omitted owing to lack of space.

## COCHISE COUNTY

California district (Hilltop).—Nearly all the output in the California district in 1942 was crude lead ore (62 tons) from the Blue Mountain and Silver Hill properties and crude silver ore (59 tons) from the Paradise No. 1 claim.

Cochise district.—Lessees operated the Republic mine near Dragoon in 1942 and shipped 925 tons of copper ore to various smelters in Arizona and 6,300 tons of zinc-copper ore to custom flotation mills in Arizona and New Mexico. The rest of the district output was 112 tons of zinc-lead ore from the Lewis property and 58 tons of copper ore from the Peacock mine.

Dos Cabezas and Tevis district.—The output of the Dos Cabezas and Tevis district in 1942 was principally gold ore (500 tons) from the

Dives mine treated in a concentration mill.

Golden Rule (Dragoon) district.—Lessees operated the Golden Rule

mine in 1942 and produced 78 tons of silver-lead-gold ore.

Hartford (Huachuca Mountains) district.—Virtually all the output in the Hartford district in 1942 was crude silver-lead ore (73 tons) from the Armistice group near Hereford.

Swisshelm district (Elfrida).—Of the total ore (2,283 tons) produced in the Swisshelm district in 1942, 2,239 tons were crude silver-lead ore from the Scribner mine; the remainder was principally high-grade

silver ore from the Silver Leaf claim.

Tombstone district.—The Tombstone Development Co. operated its mine continuously in 1942, shipped 1,130 tons of gold-silver ore and 564 tons of silver-lead ore to the smelter at El Paso, Tex., and treated 250 tons of old tailings (gold-silver) by cyanidation. At the end of the year the company had to abandon its gold-silver-lead operations, owing to Government restriction, but started opening up manganese areas for production. The rest of the district output was mainly crude silver-lead ore (1,568 tons) from the Tombstone Extension mine operated by lessees.

Turquoise district (Courtland, Pearce, Gleeson).—J. P. Giacoma operated the Defiance mine near Gleeson in 1942 and shipped 526 tons of silver-lead ore to the smelter at El Paso, Tex., and 220 tons of carbonate zinc-lead ore to an eastern zinc smelter. The remainder of the district output was largely crude lead ore (139 tons) from the Mystery and Cyclone properties and gold-silver ore (82 tons) from

the Commonwealth mine.

Warren district (Bisbee, Warren).—The principal output in the Warren district in 1942 was, as usual, copper ore from the Copper Queen branch of the Phelps Dodge Corporation; 1,111,762 tons of ore were shipped direct to the copper smelters at Douglas and Clarkdale, Ariz. The company also shipped 466 tons of gold-silver fluxing ore, 194 tons of zinc-lead ore, and 1,018 tons of copper precipitates.

According to the company-printed annual report for 1942, development and exploration during the year encountered no new large ore bodies. However, the exploration and development can be considered satisfactory, especially at the Cole and Junction mines. In November, at the request of the War Department and the War Production Board, an agreement was negotiated with Metals Reserve

Company which provides for mining marginal ores from certain areas of the Copper Queen Limestone property that are not economic at a 12-cent copper price. Metals Reserve Company pays the cost of this operation plus a small operating profit and receives the copper produced. These ores are shipped to the United Verde smelter at Clarkdale, as there is no furnace capacity for them at the Copper Queen smelter at Douglas.

The Shattuck Denn Mining Corporation operated its Denn mine and 150-ton flotation mill at Bisbee continuously; it shipped 77,857 tons of copper ore to the smelter at El Paso, Tex., and treated 14,876 tons of zinc-lead ore in the mill. This mill also treated several thousand tons of custom ore. The rest of the district output was 5,021 tons of crude ore, mainly copper ore, from the Shattuck mine operated by

lessees.

### COCONINO COUNTY

Jacob Canyon and Warm Springs district.—Lessees operated the Mackin-Kennedy-Ryan group near Jacob Lake in 1942 and shipped 1,116 tons of carbonate ore to a smelter in Utah. Other producers of similar ore were the Kaibab and Petoskey properties.

Navajo Reservation district.—About 125 tons of carbonate copper ore

were produced in 1942 from the Mardun mine east of Cameron.

#### GILA COUNTY

Banner and Dripping Springs district.—The principal output in the Banner and Dripping Springs district in 1942 was copper ore (39,837 tons) from the Christmas mine shipped direct to a smelter and zinclead ore (4,043 tons) and lead ore (620 tons) from the "79" mine. The zinc-lead ore from the "79" mine was shipped to the Denn mill at Bisbee for treatment.

Globe-Miami district.—The Globe-Miami district, with a production of 188,529,000 net pounds of copper in 1942 (164,837,300 net pounds in 1941), remained the chief copper-producing area in Arizona. The Inspiration property, with a yield of 104,320,491 net pounds of copper, was again the largest producer of copper in the district and ranked third in the State. The Inspiration Consolidated Copper Co. reported that 4,199,268 tons of copper ore from which the slimes had been removed were treated by ferric sulfate leaching; the slimes (333,784 tons) removed from the ore and 503,648 tons of additional crude copper ore were treated at the concentrator to recover the sulfide copper, and the tailings were treated with sulfuric acid to dissolve the oxide copper.

According to the printed annual report of the company for 1942, the mine, main leaching plant, slimes leaching plant, and that part of the concentrator treating slimes for the recovery of their sulfide copper content operated continuously throughout the year. The original flotation concentrator was altered during the year to provide treatment facilities for 4,000 tons of mixed crude ore a day by the leach-float process. This process involves sulfuric acid leaching of the oxide copper content of the ore, precipitating the dissolved copper as cement copper and floating it, with the sulfide copper content of the ore, as a concentrate. Treatment of crude ore by this process commenced July 13, 1942, and continued throughout the remainder of the year. Construction of a 100-ton daily capacity sulfuric acid plant was com-

おうしている おおき 人名のかいちょう あるみないない

in September and put in operation. An acute shortage of able labor continued throughout the year. A number of women employed in several sections of the plant, and their work has ed satisfactory. In October the Army furloughed 100 soldiers or underground work which, in part, alleviated the labor shortage.

The Miami Copper Co. operated its mine, 18,000-ton concentrator, and 3,000-ton leaching plant continuously; 5,922,250 tons of copper ore were treated by the leach-float process (as at Inspiration). In addition, 3,778 tons of copper precipitates were produced from leaching in place, and 426 tons of molybdenum concentrate were

recovered from the copper ore.

According to the company printed annual report for 1942, operations were continuous throughout the year in both the mixed and sulfide ore bodies and in leaching copper from broken gob overlying workedout portions of the ore body. The tonnage of ore mined was the largest (except 1930) in the 32-year life of the property, and copper production was greater than in any previous year. A shortage of labor was considerably alleviated toward the end of the year through the furloughing of essential mine labor from the Army and through the assistance of the United States Employment Service. In spite of a labor shortage, copper production was maintained at a maximum rate throughout the year at the expense of mine development, which fell behind to such an extent that a reduction in copper production is expected until such time as the necessary manpower becomes available to bring mine development back to normal, and every effort is being made in this direction. Exhaustion of the mixed-ore body, estimated to take place in the fall of 1942, has not yet occurred and it will probably continue in production through the first quarter of 1943.

The rest of the district output was largely crude copper ore (15,152

tons), principally from the Carlota mine near Miami.

The Castle Dome Copper Co., Inc., a wholly owned subsidiary of the Miami Copper Co., started in January 1942 to develop the Castle Dome ore body near Miami and to erect a treatment plant. It is expected that the mill will be completed and ore developed during the summer of 1943. The mill is straight flotation; mining is conducted by the open-cut method.

Green Valley district (Payson).—About 100 tons of gold ore were shipped in 1942 from the Summit mine dump near Payson and 5 tons

of copper ore from the Copper King claim.

Pioneer (Pinal Mountains) district.—Nearly all (58 tons) the output in the Pioneer district in 1942 was silver ore from the Bob Tail, Pioneer, and Vindicator properties south of Globe.

#### GRAHAM COUNTY

The output of Graham County in 1942 was mainly 929 tons of crude lead ore from the Aravaipa mine near Klondyke and 311 tons of similar ore from the Ten Strike claim, both in the Aravaipa district.

#### GREENLEE COUNTY

Ash Peak district (Duncan).—The output of the Ash Peak district in 1942 was 20,756 tons of silver ore shipped direct to a smelter. Leasing operations at the Ash Peak mine produced 19,041 tons, and the remainder (1,715 tons) came from the Hardy mine.

Copper Mountain district (Morenci).—The most important o in the Copper Mountain district continued in 1942 to be copper and copper precipitates from the Morenci branch of the Phelps D Corporation; the output comprised 7,640,890 tons of copper treated by concentration, 53,006 tons of copper ore shipped direct to the new Morenci smelter, and 8,986 tons of copper precipitates smelted. The rest of the district output was 837 tons of gold ore shipped to a smelter from the Climax (Emma Gomez) and Gold Belt properties and 116 tons of copper ore from the Keating mine.

According to the annual report of the Phelps Dodge Corporation for 1942, regular production from the Morenci open pit commenced at the end of January, and the new 25,000-ton concentrator received its first ore January 30. The initial charging of the first smelter furnace started in April, and full capacity of all operations occurred Until July a portion of the concenin the following 6-week period. trate production was shipped to the Copper Queen smelter at Douglas. Production of copper from leaching operations was increased in 1942 by the output from the new Metcalf precipitation plant, which treats copper-bearing waters from the old Coronado mine. At the close of the year, 15 mining benches were operated at the open pit. In March 1942 the corporation concluded negotiations with the Defense Plant Corporation for enlargement of operations at the Morenci open pit and reduction works and also of the capacity of the El Paso copper It is estimated that construction work on the program will be completed about August 1, 1943, and that the new facilities will be operating at capacity some time during the last quarter of the year.

#### MARICOPA COUNTY

Cave Creek and Camp Creek district.—Virtually all the output in the Cave Creek and Camp Creek district in 1942 was gold ore; most of it (210 tons) was from the Maricopa mine, treated by amalgamation.

New River (Moors) district.—The Orizaba Mining Co. operated the Orizaba mine in 1942 and shipped 1,898 tons of copper ore to a smelter. A little gold ore was shipped from the Leland, Minnie Lee, and Moore properties.

Osborn district.—A total of 1,624 tons of ore was produced from two mines in the Osborn district in 1942; the output comprised 1,155 tons of crude lead ore from the Moon Anchor mine and 434 tons of lead ore and 35 tons of lead-copper ore from the Belmont-McNeil mine.

Salt River Mountains district.—The Park View Mining Co. operated the Delta mine near Phoenix 4 months in 1942; about 450 tons of gold ore were treated in a flotation mill, and 211 tons of similar ore were shipped to a smelter. Gold ore was produced also from the North Delta claim.

Sunflower (Mazatzal) district.—A lessee operated the Little Daisy mine 3 months in 1942 and shipped 52 tons of gold ore to a smelter.

Vulture district.—Gold ore (34,143 tons) from the Vulture mine was again the most important output in the Vulture district in 1942. The East Vulture Mining Co. operated the mine and its 300-ton

The Real Property of

cyanide and concentration mill continuously until December 15. The rest of the district output was mainly lead ore (926 tons) from the Montezuma mine and silver ore (269 tons) from the Newsboy (Pitt) mine.

Wickenburg district.—About 1,000 tons of old tailings (gold) from

a dump near Wickenburg were treated in 1942 by cyanidation.

#### MOHAVE COUNTY

Bentley (Grand Wash) district.—Carbonate ore (36 tons) averaging 26 percent copper to the ton was shipped in 1942 from the Grand

Gulch mine.

Cedar Valley district.—Molybdenum Corporation of America operated the Boriana mine near Yucca throughout 1942 and treated 10,000 tons of tungsten-copper ore by gravity concentration and flotation; copper concentrates were shipped to a smelter in Arizona and tungsten concentrates to an eastern market.

Cottonwood district.—Lessees operated the Copper Giant mine near Hackberry in 1942 and shipped 2,030 tons of gold-copper ore to a

smelter.

Gold Basin district.—Nearly all the output of the Gold Basin district in 1942 was gold ore and old tailings treated in a custom cyanide mill; the chief producers were the O. K., Excelsior, and Golden Link properties. Placer gold (19 fine ounces) was recovered by various operators working at the Gold Basin Placers.

Indian Secret (White Hills) district.—A 40-ton cyanide leaching plant was built in 1942 at the White Hills property, and during the

year 250 tons of silver ore were treated.

Maynard and McConnico district.—Mining and milling at the Bimetal open-pit mine near Kingman ceased in January 1942; before closing about 100 tons of gold ore were treated by flotation. The rest of the district output was 25 tons of gold ore from the Columbus-Lead Carbonate group.

Minnesota district.—The output of ore in the Minnesota district totaled 171 tons in 1942; most of it was gold-silver ore cyanided from the Horn Silver mine and gold ore cyanided from the Blue Rock

mine.

Music Mountain district.—Lessees operated the Mohawk mine near Valentine in 1942 and treated 153 tons of gold ore by amalgamation and concentration. The remainder of the district output was principally rich gold ore (74 tons) from the Roosevelt mine, shipped to a smelter.

Owens (McCracken and Potts Mountain) district.—The Cleopatra mine was operated nearly all year by Strong & Harris, who shipped 2,798 tons of gold-copper ore to the smelter at Clarkdale. The rest of the district output was mainly small lots of gold ore and coppergold ore produced from various claims and sold to the Wickenburg Ore Market.

San Francisco (Oatman, Goldroad, Katherine, Vivian) district.— Production of gold in the San Francisco district was 28,570 fine ounces in 1942 compared with 42,098 fine ounces in 1941. More than 74 percent of the output came from the Goldroad mine at Goldroad and most of the remainder from the Tyro mine at Katherine. The United States Smelting, Refining & Mining Co. operated the Goldroad mine continuously until September 20 and treated 99,298 tons of gold ore in the company 300-ton cyanide plant. The Tyro mine and 300-ton cyanide mill of the Gold Standard Mines Corporation were operated throughout the year; the company treated 77,089 tons of low-grade gold ore from the Tyro mine and 510 tons of custom ore. The Vivian Mining Co. operated its 100-ton custom cyanide mill until March 1; about 1,450 tons of gold ore were treated, principally from the Vivian-Lelande-Mitchell and Pioneer properties. Other gold producers included the Big Jim, Burt, Gold Dust, King of Secret Pass, Minnie,

Philadelphia, Ruth-Rattan, and Telluride properties.

Wallapai district (Cerbat, Chloride, Mineral Park, Stockton Hill).— Approximately 70,500 tons of ore were produced in the Wallapai district in 1942; nearly 57 percent of it was zinc-lead ore from the Tennessee mine, 26 percent was zinc ore from the Middle Golconda-Oro Plata group, and the remainder was largely gold ore from various properties. The Tennessee mine at Chloride was operated throughout the year by the Tennessee-Schuylkill Corporation; 40,055 tons of zinclead ore were treated in the company 150-ton flotation mill. Davenport Mining & Reduction Co. operated the Middle Golconda-Oro Plata group continuously until September 11, when operations ceased, owing to a shortage of available labor. During the year 18,636 tons of zinc ore were treated in the company 100-ton flotation About 2,800 tons of gold ore from the Golden Gem mine were concentrated in a mill on the property, and 1,026 tons of similar ore from the mine dump were cyanided in a custom mill. Silver ore (1,000 tons) from the C. O. D. mine was concentrated, a total of 1,076 tons of gold-silver ore from the Juno and Nighthawk mines was cyanided, and 446 tons of zinc-lead ore from the Minnesota-Connor property were concentrated. Other producers of gold ore included the Emerson, Flores, Hidden Treasure, O'Brien, Rambler, Red Seal, Rico, and Summit properties.

Weaver (Mocking Bird, Pilgrim, Portland) district.—Output of ore in the Weaver district declined from 18,858 tons in 1941 to 3,861 tons in 1942. The principal output in 1942 was 3,733 tons of gold ore from the Golden Door mine treatèd in the custom cyanide mill of Producers Mines, Inc. This company operated its 300-ton cyanide mill continuously on custom ore until May 15, when it closed

permanently.

#### PIMA COUNTY

Ajo district.—The New Cornelia open-pit mine, the only producer in the Ajo district in 1942, was operated at capacity throughout the year by the Phelps Dodge Corporation; 8,324,033 tons of copper ore were treated by flotation, and 704 tons of crude copper ore were shipped direct to a smelter. The capacity of the concentrator was increased from 22,500 to 25,000 tons of ore a day, and the mine remained the largest producer of copper in Arizona. According to the annual report of the corporation for 1942, necessary work was done in the open pit with a view to meeting the increased production problem; double tracking was done on several of the waste dumps. At the concentrator certain structural changes in milling equipment, designed to increase production still further, were completed and satisfactory results obtained.

A CONTRACTOR OF THE PROPERTY OF THE PARTY OF

The Maria of the Contraction of

Amole district.—Virtually all the output of the Amole district in 1942 was crude lead ore (607 tons) from the Old Yuma mine near Tucson; the property was worked part of the year by the Tucson Ore Milling Co.

Arivaca district.—Gold ore (70 tons) shipped to a smelter from the Backbone and Oreona mines was the chief output in the Arivaca

district in 1942.

Baboquivari district.—All the output (1,700 tons) in the Baboquivari district in 1942 was gold ore from the Allison mine, operated by the Gold Bar Mining Co.; both the mine and 50-ton cyanide mill shut

down March 1.

Cababi (Comobabi) district.—About 85 tons of ore were produced in the Cababi district in 1942; most of it was copper ore from the Serenake mine, gold ore from the Grand Central mine, and lead ore from the Stepp claim.

Cerro Colorado district.—Silver ore (62 tons) and lead-copper ore

(5 tons) were produced in 1942 from the Mary "G" mine.

Empire district.—E. P. Hilton operated the State of Maine mine in 1942 and shipped 145 tons of carbonate lead ore to El Paso, Tex., and

429 tons of carbonate zinc ore to Coffeyville, Kans.

Helvetia (Rosemont) district.—The Helvetia Mining & Milling Co. was organized in 1942 to operate the Copper World (Leader) mine; during the year 2,000 tons of copper ore were treated in a concentration mill, and 1,599 tons of similar ore were shipped direct to a smelter. Copper ore (855 tons) was shipped also from the Rosemont mine by a lessee and lead-copper ore (11 tons) from the Mohawk claim.

Old Hat district (Oracle).—Three mines in the Old Hat district in Pima County produced 12,149 tons of copper ore in 1942; most (12,000 tons) of it was treated in a 100-ton flotation mill and came from the Daily and Geeseman groups operated by Control Mines, Inc.

Pima (Sierritas, Papago, Twin Buttes) district.—Nearly all the output in the Pima district in 1942 was crude silver-lead ore (96 tons) from the Esperanza, High Hill, and Two Friends properties and crude copper ore (65 tons) from the Armargoza, Copper Glance, and King properties.

Quijotoa district.—Copper ore (35 tons) was produced in 1942 from the Highland and Coplen mines and lead ore (30 tons) from the Tres

Metals claim.

Roskruge and Waterman (Silver Hill) district.—Leasing operations at the Silver Hill mine in 1942 produced 145 tons of silver-lead ore

and 44 tons of copper ore.

Silver Bell district.—George T. Harford operated the Arizona Copper & Mint property in 1942 and shipped 100 tons of silver-lead-copper ore to a smelter.

PINAL COUNTY

Bunker Hill district (Copper Creek).—The Bunker Hill and Magma Chief properties were operated in 1942; 370 tons of lead-copper ore from the Bunker Hill mine were concentrated, and 210 tons of copper

ore from the Magma Chief mine were shipped direct to a smelter.

Casa Grande district.—The output of the Casa Grande district in 1942 comprised 253 tons of silver ore from the Silver Reef mine, 89 tons of gold ore from the Old Jonah and Turning Point mines, 57 tons of copper ore from the Slate Mountain and Andrade properties, and 44 tons of lead ore from the Sheridan Range and Sunrise properties.

Mineral Creek district (Ray).—Nevada Consolidated Copper Corporation (subsidiary of Kennecott Copper Corporation) operated its mine at Ray and 12,000-ton concentrator at Hayden at capacity throughout the year; 2,967,941 tons of copper ore were treated by flotation, and 1,327 tons of crude copper ore and 8,371 tons of copper precipitates were shipped to the smelter at Hayden. The rest of the district output was 276 tons of copper ore from the Copper Butte mine.

Mineral Hill district.—The principal output in the Mineral Hill district in 1942 was gold ore (1,079 tons) shipped to a smelter from the

Consolidated Gold, Sunset, and Wedge properties.

Old Hat district (Oracle).—In June 1942 the Mammoth-St. Anthony Limited installed additional flotation equipment in its 550-ton mill to treat sulfide zinc-lead ore; heretofore, the mill had treated only oxidized gold-silver-lead-molybdenum-vanadium ore. During the year 147,293 tons of such ore were treated by gravity concentration, followed by flotation, the flotation tailings were treated by cyanidation, and 15,700 tons of zinc-lead ore were treated by straight flotation. The oxide lead concentrates were smelted in the company 20-ton lead furnace, and the sulfide lead concentrates were shipped to El Paso, Tex. Gold precipitates, as well as molybdenum and vanadium products, were shipped East and zinc concentrates to Amarillo, Tex. The rest of the district output was mainly 45 tons of crude lead ore from the Mammoth Tiger Extension mine.

Pioneer district (Superior).—Copper ore and zinc-copper ore from the Magma mine continued in 1942 to be the principal output in the Pioneer district. The Magma Copper Co. operated its mine, 850-ton concentrator, and 450-ton copper smelter throughout the year, except for brief shut-downs to allow for repairs. The company reported that 281,283 tons of copper ore and 87,105 tons of zinc-copper ore were treated in the concentrator, and 77,728 tons of copper ore were sent direct to the smelter. The zinc concentrates (8,748 tons) were shipped

to Amarillo, Tex.

According to the company printed annual report for 1942, the average net cost of producing copper after deduction of gold, silver, and zinc concentrate values was 9.66 cents a pound compared with 7.90 cents a pound in 1941. Development in 1942 comprised 8,647 feet of drifting, 4,985 feet of raising, 749 feet of sinking, and 4,073 feet of cross-cutting; the shaft is now down to the 4,908 level. During the summer months production of ore dropped because of four retarding factors—excessive heat throughout the lower levels of the mine, loss of many skilled employees to other higher-paid war industries and to the armed forces, inexperience and inefficiency of many of the labor replacements, and inability to obtain a sufficient number of labor replacements of any kind from August to October. In October the company obtained some experienced miners released from the Army and some gold miners from the Colorado gold mines closed by Government regulations. Commencing with October production increased; however, it took approximately 10 percent more men underground to attain this increase. The tonnage of zinc-copper ore mined in 1942 was greater than in any previous year, but during December 1942 to June 1943 the zinc content of the ore has diminished greatly; the gold and silver content of the copper ore on the lower levels of the mine has also decreased seriously.

The rest of the district output was mainly crude silver ore (8,096 tons) from the Reymert mine, crude gold ore (759 tons) from the Lake Superior & Arizona property, and silver ore (601 tons) from the Belmont and Queen Creek properties.

#### SANTA CRUZ COUNTY

Harshaw district.—In 1942, as in 1941, the principal output in the Harshaw district was zinc-lead-silver ore from the Trench and Flux groups operated by the American Smelting & Refining Co. The company 200-ton flotation mill ran continuously and treated 76,855 tons of zinc-lead-silver ore; it was the largest producer of lead and zinc in Arizona in 1942. The rest of the district output was crude silver-lead ore (297 tons) from the American, Hardshell, and World's Fair properties.

Oro Blanco district (Ruby).—About 1,800 tons of ore were produced in the Oro Blanco district in 1942; most of it was crude silver ore (1,133 tons) from the Brick mines, gold ore (269 tons) from the Noon and Oro Blanco properties, and gold-silver ore (237 tons) from the Old

Soldier and Tres Amigos group.

Patagenia (Duquesne) district.—In 1942 zinc-lead-copper ore from the Duquesne mine, operated by the Callahan Zinc-Lead Co., was the most important output in the Patagonia district. The company 125-ton flotation mill ran continuously and treated 31,136 tons of zinc-lead-copper ore (including 967 tons of custom ore); copper concentrates (1,432 tons) and lead-copper concentrates (1,016 tons) were shipped to El Paso, Tex., and zinc concentrates (4,011 tons) to Amarillo, Tex. The remainder of the district output was chiefly zinc-lead-copper ore (967 tons) from the Pride of the West mine treated in the Duquesne mill.

Tyndall district.—The output of the Tyndall district in 1942 was principally crude lead ore (207 tons) and zinc-lead milling ore (337 tons) from the Jefferson mine, and silver-lead ore (238 tons) from the

Alto and Eureka properties.

Wrightson district.—Lead-copper ore (30 tons) was produced in 1942 from the Armada mine and lead ore (7 tons) from the Lead King claim.

#### YAVAPAI COUNTY

Agua Fria district.—All the output of the Agua Fria district in 1942 was crude copper ore (450 tons) from the Burzog (Old Minor) and

Stoddard properties east of Mayer.

Big Bug district.—The principal output in the Big Bug district in 1942 was, as in 1941, zinc-lead ore and gold-silver ore from the Iron King mine at Humboldt. The mine was operated continuously—the first 6 months of 1942 by the Iron King Mining Co. and the last 6 months by the Shattuck Denn Mining Corporation, which purchased the property July 1; 76,757 tons of zinc-lead ore were treated in the company 240-ton flotation mill, 65,018 tons of current flotation tailings (gold-silver) were treated by cyanidation, and 12,393 tons of crude gold-silver ore were shipped to a smelter. The remainder of the district lode output was largely old tailings (1,298 tons) containing gold, silver, and copper shipped from the Humboldt tailing dump. More than one-half of the State placer gold production in 1942 was

recovered from properties in this district; the chief producer was the Arical Mines, Inc., operating a dragline floating dredge at the Black

.Walnut, Farnum, and Shanks properties.

Black Canyon district.—The Golden Turkey Mining Co., Inc., a large producer of gold from 1933 to 1941, inclusive, closed its mine and 200-ton mill near Cordes in January 1942; the mill treated 1,140 tons of gold ore in 1942. The rest of the district output was mainly gold-silver ore (33 tons) from the Hidden Treasure mine and silver ore (30 tons) from the Thunderbolt mine.

Black Hills district.—The output of the Black Hills district in 1942 was 245 tons of gold ore from the Ambassador and D. & M. properties

near Dewey and 32 tons of copper ore from the Yaeger mine.

Black Rock district.—The Super X (Atos) mine near Wickenburg was worked until May 31, 1942, and 900 tons of gold ore were treated by cyanide leaching. The remainder of the district output was chiefly crude gold ore (376 tons) from the George Washington, Gold Crown, and Golden Gate properties.

Blue Tank district.—Leasing operations at the Franklin D. mine produced 43 tons of gold ore in 1942, and 9 fine ounces of placer gold were recovered from claims along the Hassayampa River.

Bullard (Pierce) district.—Virtually all the output in the Bullard district in 1942 was crude gold-copper ore (289 tons) from the Bullard and Metz properties near Aguila.

Castle Creek district.—Small lots of various classes of ore were produced from claims in the Castle Creek district in 1942 and sold

to the Wickenburg Ore Market.

Cherry Creek district.—Eight mines in the Cherry Creek district produced a total of 258 tons of crude gold ore in 1942; the chief producers were the Gray Eagle, Bugler, Sitting Bull, Black Hawk, and

Volcano properties.

Copper Basin district.—The Commercial mine near Skull Valley was worked by a lessee in 1942, and 9,167 tons of copper ore were shipped to a smelter. The rest of the district lode output was mainly sulfide zinc ore (230 tons) from the Boston-Arizona mine and highgrade gold ore (15 tons) from the Stanley A. claim. About 15 fine ounces of placer gold were recovered from various claims along

Copper Basin Wash.

Eureka district.—Copper ore from the Bagdad mine, operated by the Bagdad Copper Corporation, was the principal output in the Eureka district in 1942; 56,392 tons of ore were treated in the company 250-The company also built a new 2,500-ton mill and ton flotation mill. prepared the mine for greatly increased output in 1943. The Hillside mine—a large producer of gold, silver, lead, and zinc in 1941—was shut down in January 1942; during the month about 3,000 tons of zinc-lead ore were treated by flotation. Later in the year a lessee operated the mine and shipped 200 tons of crude gold-silver ore to a The remainder of the district output was chiefly gold ore (377 tons) from the April Showers, Big Stick, Bland, Crosby, Homestake, and New Year properties.

Hassayampa (Groom Creek, Hassayampa River, Senator, Prescott) district.—Seventeen lode mines in the Hassayampa district produced 285 tons of ore in 1942; most of it was gold ore (205 tons) shipped direct to a smelter from the Eureka, Golden Summer, Independence,

The output of placer gold Oro Flame, and Railroad properties. totaled 546 fine ounces, which was recovered chiefly at the Hobbs property by a dragline floating dredge during the first 2 months of the year.

Kirkland district.—The only output in the Kirkland district in

1942 was 47 tons of gold ore from the Venus mine.

Lynx Creek district.—The output of placer gold in the Lynx Creek district decreased from 4,372 fine ounces in 1941 to 87 fine ounces in 1942; most of the gold in 1942 was recovered by a dry-land dredge

in January at the Speck-Lynx Creek property.

Martinez (Congress) district.—The Congress Mining Corporation, a large producer of gold since 1938, closed its 300-ton cyanide mill May 1, 1942. During the first 4 months of the year the mill treated 32,800 tons of gold ore and old tailings from the Congress property. From June 1 to the end of the year lessees worked in the mine and shipped 378 tons of crude gold ore to a smelter. The rest of the district output was mainly 600 tons of gold ore (concentrated) from the Niagara-Congress waste dump.

Peck district.—Virtually all the output in the Peck district in 1942 was crude silver ore (204 tons) shipped to a smelter from the Battle

Flat and Swastika mines near Crown King.

Pine Grove district (Crown King).—The most important producer in the Pine Grove district in 1942 was, as in 1941, the Gladiator-War Eagle group operated by the Gladiator Mining Co. During the first 7 months of the year 1,952 tons of crude gold ore were shipped direct to a smelter; in August the company completed the erecting of a 50-ton mill, and during the remainder of the year 2,500 tons of zinclead-gold ore were treated by flotation. Lead concentrates containing an average of 6.31 ounces of gold to the ton were shipped to El Paso, Tex., and zinc concentrates to Amarillo, Tex. The rest of the district output was mainly 206 tons of crude gold-lead ore from the Del Pasco mine.

Pocket Creek district:-Sluicing at the Pocket Creek Placer in 1942

recovered 201 fine ounces of gold and 7 fine ounces of silver.

Tiger district.—Six mines in the Tiger district produced 263 tons of ore in 1942; most of it was gold ore (153 tons) from the Fortuna, Pilgrim, and Snowdrift properties and silver ore (100 tons) from the Tiger mine.

Verde district (Jerome).—The principal output in the Verde district in 1942 was, as usual, copper ore from the United Verde mine of the Phelps Dodge Corporation. The mine and 2,100-ton concentrator were operated throughout the year; 563,140 tons of copper ore and old tailings and 413 tons of copper precipitates were shipped direct to the company smelter at Clarkdale, and 649,108 tons of copper ore were treated in the concentrator.

According to the printed annual report of the corporation for 1942 ore production at the United Verde mine was confined to the underground areas. By the end of the year all copper mining areas above the 1,650 level had been abandoned on account of depletion of available ores. The development program for the lower levels was pushed, and the No. 8 shaft sinking was completed to the 4,631 level. adjustment of the production quota for the United Verde mine under

the premium-price plan made it possible to make a moderate increase in copper production by mining certain marginal or low-grade ores

during the last quarter of the year.

Lessees continued to work the Iron King-Equator group and shipped 24,477 tons of siliceous gold-silver ore to a smelter. The rest of the district output was chiefly 4,012 tons of crude copper ore from the Dundee-Arizona mine and 1,337 tons of crude gold-silver ore from

the Silver Plate property.

Walker district.—The French Sheldon Mines operated the Sheldon property until October 20; about 1,000 tons of gold-silver ore were treated in the 100-ton concentration mill, and 1,036 tons of crude gold ore were shipped to a smelter. The remainder of the district lode output was largely 377 tons of zinc-lead milling ore from the New Strike mine and 341 tons of high-grade gold ore shipped to a smelter from the Champion, Emma, Good Luck, Lost Wonder, and Oro Plata properties. Approximately 20 fine ounces of placer gold were

recovered from various claims on Lynx Creek near Walker.

Weaver district (Octave).—The principal output in the Weaver district in 1942 was, as usual, gold ore from the Alvarado, Octave, and Yarnell properties. However, the Octave mine, the largest producer of gold in the district since 1934, was closed in December, the Alvarado in June, and the Yarnell in September. The 80-ton flotation mill at the Octave mine treated 24,188 tons of gold ore, and the flotation tailings (23,718 tons) were cyanided. In addition, 471 tons of crude gold ore were shipped to a smelter. The Alvarado mine and 100-ton mill were worked by the Liberty Hill Gold Mines until June 30; 18,993 tons of gold ore were treated by cyanide leaching. About 26,500 tons of similar ore from the Yarnell mine were treated also by cyanide leaching. The remainder of the district lode output was chiefly gold ore (267 tons) shipped to a smelter from the Monica, May Queen, and Turtle properties. The output (56 fine ounces) of placer gold was recovered from various claims along Weaver Creek and at Rich Hill.

White Picacho district.—Nearly all the output in the White Picacho district in 1942 was silver-lead ore (1,155 tons) shipped to a smelter

from the Diamond Joe mine near Wickenburg.

#### YUMA COUNTY

Castle Dome district.—The Arizona Lead Co. leased the Eliza DeLuce group in 1942 and built a 100-ton concentration mill on the property; from August 13 to the end of the year the mill treated 11,007 tons of silver-lead ore and old tailings. The rest of the district output was mainly 111 fine ounces of placer gold recovered by a Stebbins dry concentrator at the Ocatilla property.

Cienega district.—Leasing operations at the Empire Arizona and Mavis properties near Parker produced 826 tons of crude gold-copper

ore in 1942.


Ellsworth district (Salome).—About 640 tons of ore were produced in the Ellsworth district in 1942; most of it was crude gold-copper ore (436 tons) from the Centroid, Critic, Moore, Sheba, and Yuma Copper properties and crude gold ore (100 tons) from the Bunker Hill and Hercules mines.

The second secon

Plomosa district.—Nearly all the lode output in the Plomosa district in 1942 was crude silver ore (984 tons) from the R. & A. mine and crude gold ore (847 tons) and crude gold-copper ore (67 tons) from the Little Butte mine near Bouse. The output of 51 fine ounces of placer gold was recovered chiefly from the Can Do (Erdman), Cave Creek, and Sax properties.

Santa Maria (Planet, Bill Williams) district.—The Swansea Development Co. worked the Swansea mine throughout the year and shipped 293 tons of crude copper ore to a smelter. The property is equipped with a 250-ton flotation mill, and plans were made in

December to bring the mine back to capacity production.



## GOLD, SILVER, COPPER, LEAD, AND ZINC IN CALIFORNIA

(MINE REPORT)

By CHARLES WHITE MERRILL AND H. M. GAYLORD

## SUMMARY OUTLINE

	F Page		Page
Summary	261	Mining industry	269
Calculation of value of metal production	262	Ore classification	270
Mine production by counties	007	Ore classification  Metallurgic industry  Review by counties and districts	271
wine production by countries	. 201	Review by counties and districts	276

#### SUMMARY


The 39-percent decline in the total value of California output of gold, silver, copper, lead, and zinc in 1942 compared with 1941 does not nearly picture the disastrous effect of war on the industry. The production rate in December sank below the monthly average for any year since 1848. Gold, silver, and copper output in 1942 was below 1941 levels, but lead and zinc production rose. Higher wages, enlistment of miners in the armed forces, migration of miners to war industries, rising prices of supplies and equipment and difficulties in obtaining them, increased taxes, and the fixed prices for gold and silver (the most important of the five metals in California) were factors accelerating the downward trend, which was already under way in 1941. Although War Production Board Order L-208 popularly was assigned as the cause of the great decline in California's gold industry, a review of the 1941-42 monthly production record does not substantiate this view. The recession was virtually uninterrupted for the 2 years, and the rate of decline in October and November 1942, when the order was taking effect, did not deviate from the general 2-year pattern. (See Gold and Silver chapter of this volume for text of Order L-208.)

Comparing 1942 with 1941, gold decreased 40 percent and silver 33 percent in both quantity and value; copper decreased 73 percent in quantity and 72 percent in value; lead increased 49 percent in quantity and 75 percent in value; and zinc increased 39 percent in quantity and 73 percent in value. Of the total value of the five metals in 1942, gold represented 93 percent, silver 3 percent, lead 2

percent, and copper and zinc 1 percent each.

Despite a 42-percent slump for 1942 in total value of production, Nevada County continued to be the largest contributor to the metalmining output of California; it supplied 18 percent of the State total value of the five metals, 19 percent of the total gold, and 40 percent of the lode gold. Sacramento County (largely from gold dredging) contributed 14 percent of the total value of the five metals; Yuba County (largely from gold dredging) and Kern County (largely from gold ore

and old tailings), 8 percent each; Butte County (largely from placer gravels), 7 percent; Amador County (largely from gold ore) and Inyo County (from gold, lead, tungsten, and zinc ores), 5 percent each; Siskiyou County (largely from placer gravels), 4 percent; and Calaveras County (from gold ore, gravels, and copper ore) and Mariposa County (two-thirds from gold ore and one-third from gravels), 3 percent each. Thus, each of the foregoing 10 of the 36 counties producing the five metals in California in 1942 contributed over 1 million



W. I.

FIGURE 1.—Value of mine production of gold, silver, and copper and total value of gold, silver, copper, lead, and zinc in California, 1848-1942. The value of lead and zinc has exceeded \$1,000,000 in only a few years.

dollars worth; together, they supplied over three-fourths of the total for these metals.

All tonnage figures are short tons and "dry weight"; that is, they do not include moisture.

Yardage figures used in measuring material treated in placer operations are "bank measure": that is, the material is measured in the ground before treatment.

The value of metal production herein reported has been calculated at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zinc
1938	Per fine ounce \$35.00 35.00 35.00 35.00	Per fine ounce 5 \$0.646+ 6.678+ 7.711+ 7.711+ 7.711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057 .067	Per pound \$0.048 .052 .063 .075

¹ Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.
² Treasury buying price for newly mined silver.
² 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.
¹ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.
² \$0.64646464.

Mine production of gold, silver, copper, lead, and zinc in California, 1938-42, and total, 1848-1942, in terms of recovered metals

Year		Mines produc- ing <sup>1</sup>		Ore, old tailings,	Gold (lode	e and placer)	Silver (lode and placer)		
		Lode	Placer	etc. (short tons)	Fine ounces	Value	Fine ounce	s Value	
1938		927 1, 028 1, 030 835 434	676 749 836 724 428	4, 648, 249 5, 577, 853 4, 669, 433 4, 280, 185 2, 503, 198	1, 311, 129 1, 435, 264 1, 455, 671 1, 408, 793 847, 997	\$45, 889, 515 50, 234, 240 50, 948, 485 49, 307, 755 29, 679, 895	2, 590, 804 2, 599, 139 2, 359, 776 2, 154, 188 1, 450, 440	1, 764, 264 1, 678, 063 1, 531, 867	
1848-1942				(2)	101, 110, 756	2, 240, 980, 112	104, 482, 628	84, 367, 327	
		Copper			Lead	Ziı	ıc		
Year -	Por	inds	Value	Pounds	Value	Pounds	Value	Total value	

	Co	pper	Le	ead	. 2	Total value	
Year	Pounds	Value	Pounds	Value	Pounds	Value	10tal value
1938	1, 612, 000 8, 360, 000 12, 876, 000 7, 886, 000 2, 116, 000	\$157, 976 869, 440 1, 454, 988 930, 548 256, 036	990, 000 1, 052, 000 3, 544, 000 6, 928, 000 10, 302, 000	\$45, 540 49, 444 177, 200 394, 896 690, 234	12,000 158,000 880,000 1,226,000	\$624 9, 954 66, 000 114, 018	\$47, 767, 894 52, 918, 012 54, 268, 690 52, 231, 066 31, 771, 607
1848-1942	³ 593, 628	192, 459, 604	<sup>8</sup> 131, 003	15, 455, 155	<sup>8</sup> 53, 096	9, 569, 482	2, 542, 831, 680

<sup>1</sup> Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to property.

2 Figures not available.

3 Short tons.

Gold produced at placer mines in California, 1938-42, by classes of mines and by methods of recovery, and total, 1848-1942 1

			Material	G	old recovered	
Class and method	Mines produc- ing 2	Washing plants (dredges)	treated (cubic yards)	Fine ounces	Value	Average per cubic yard
Surface placers: Gravel mechanically handled: Connected-bucket dredges:						
1938	33 34 32 37	48 47 46 47	117, 080, 000 121, 655, 000 132, 461, 000 135, 757, 000	375, 296 370, 264 414, 966 418, 282	\$13, 135, 360 12, 959, 240 14, 523, 810 14, 639, 870	\$0.112 .107 .110 .108
1942 Dragline dredges:	30	44	106, 543, 000	310, 937	10, 882, 795	. 102
1938 1939 1940 1941	77 142 198 234	68 109 106 112	24, 560, 000 31, 618, 000 42, 747, 000 45, 579, 000	118, 108 172, 519 205, 181 225, 019	4, 133, 780 6, 038, 165 7, 181, 335 7, 875, 665	. 168 . 191 . 168 . 173
1942 Becker-Hopkins dredges:	122	79	24, 526, 000	117, 906	4, 126, 710	. 168
1940.3 19411942	2 3 1	2 2	35, 000 52, 000 5, 000	148 244 23	5, 180 8, 540 805	.148 .164 .161
Suction dredges: 4 1940 3 1941 1942	4 17 18	4 17 15	64, 000 357, 000 278, 000	584 1, 763 1, 419	20, 440 61, 705 49, 665	. 319 . 173 . 179
Nonfloating washing plants: \$ 1938	74 114 131 85 46	71 101 105 76 40	3, 538, 000 5, 512, 000 5, 908, 000 5, 656, 000 1, 637, 000	23, 046 41, 694 28, 232 28, 703 10, 044	806, 610 1, 459, 290 988, 120 1, 004, 605 351, 540	. 228 . 265 . 167 . 178 . 215

See footnotes at end of table.

Marie Committee Committee

Gold produced at placer mines in California, 1938-42, by classes of mines methods of recovery, and total, 1848-1942 1—Continued

	Mines	XX	Material	(	Gold recovered	
Class and method	produc- ing?	Washing plants (dredges)	treated (cubic yards)	Fine ounces	Value	Average per cubic yard
Surface placers—Continued. Gravel hydraulically handled:						
Hydraulic:	1 / 11	ŀ	1.00			1
1938	86		1,719,000	7,061	247, 135	\$0.14
1939	74		921, 000	6,059	212,065	. 23
1940	92	[	2, 401, 000	12,059	422, 065	.17
1941	. 79		2, 886, 000	10,145	355, 075	.12
1942	45		1, 980, 000	6, 106	213,710	.10
Small-scale-hand methods: 6 Wet:						
1938	292		2, 863, 500	41,686	1, 459, 010	. 510
1939			2, 534, 100	38, 815	1, 358, 525	. 536
1940			1,710, 200	38, 526	1, 348, 410	.78
1941			1, 599, 700	29.040	1,016,400	.63
1942	119		1, 152, 900	16,079	562, 765	. 48
Dry:		1.5		1		
1938	15		6,500	172	6,020	. 92
1939	25			169	5, 915	.49
1940	17		10,800	211	7,385	.68
1941	13		7,300	220	7,700	1.05
1942	7		1,100	73	2, 555	2.32
Underground placers:						
Drift:						
1938	99		97,000	7, 144	250, 040	2, 578
1939	94		83,000	6, 525	228, 375	2. 75
1940	96		88,000	5, 045	176, 575	2.00
10/1	74		90,000			
1941 1942	45		22,000	4, 597 2, 339	160, 895 81, 865	1.788 3.72
***************************************			22,000	2, 009	01,000	3. 12.
Grand total placer:	1					
1938	676		149, 864, 000	572, 513	20, 037, 955	. 134
1939	7 749		162, 335, 000	636, 045	22, 261, 575	.13
1940	7 836		185, 425, 000	704, 952	24, 673, 320	. 133
1941			191, 984, 000	718.013	25, 130, 455	. 13
1942	7 428		136, 145, 000	464, 926	16, 272, 410	.120
848-1942 1			(8)		1, 410, 915, 026	(8)

<sup>1</sup>[For historic data by years see Minerals Yearbook, Review of 1940, p. 219. <sup>2</sup> Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to

2 Excludes titinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to property worked.
3 First year for which this method was reported used in California.
4 Includes all placer operations using suction pump for delivering gravel to floating washing plant, except those producing less than 100 ounces of gold which are included under "Small-scale hand methods."
4 Includes all placer operations using power excavator and washing plant, both on dry land; when washing plant is movable, outfit is termed "dry-land dredge."
6 Includes all operations in which hand labor is principal factor in delivering gravel to sluices, long toms, dip boxes, pans, rockers, dry washers, etc.
7 A mine using more than 1 method of recovery is counted but once in arriving at total for all methods.
8 Complete data not available.

Gold.—An uninterrupted rise beginning in 1929 culminated in the production of \$50,948,485 in gold in 1940, the largest value since 1856. In 1941, however, a reaction set in and gained headway in 1942. Monthly production declined approximately 4 percent a month fairly regularly from January 1941 to May 1942, when the downward trend greatly accelerated and continued at about 16 percent a month to December 1942. Strangely, the period when War Production Board Order L-208 was becoming effective did not mark a substantial change Apparently, economic forces were curtailing gold production so rapidly in 1942 that exercise of Federal authority was not needed to accomplish a most drastic curtailment in gold mining in Production in December was at an annual rate of 246,612 fine ounces or \$8,631,420, which, except for 1929 (when California

gold output was valued at \$8,526,703), represented the lowest level

since 1848.

The 25 leading gold-producing mines in California in 1942, listed in the following table, yielded 60 percent of the total gold output of the State. In 1942, six placers (five connected-bucket dredges and one dragline dredge) and two lode mines (gold ore) displaced two placers (connected-bucket dredges) and six lodes (five gold ore and one copper ore). Of those displaced, none was working at the end of 1942. Of those on the 1942 list, only four were producing at the close of the year.

Twenty-five leading gold-producing mines in California in 1942, in order of output

Rank	Mine	District	County	Rank in 1941	Operator	Source of gold
1 2	Natomas Co Yuba Unit	FolsomYuba River	Sacramento Yuba	2 4	Natomas CoYuba Consolidated Gold Fields.	Dredge. Do.
3	Idaho Maryland-	Grass Valley- Nevada City.	Nevada		Idaho Maryland Mines Corporation.	Gold ore.
4		do			Empire Star Mines Co., Ltd.	Do.
5	Lava Cap	do		1	Lava Cap Gold Min-	Do.
6	Capital dredges Butte Unit	FolsomOroville	Sacramento Butte		Capital Dredging Co Yuba Consolidated Gold Fields.	Dredge. Do.
8	Golden Queen	Mojave	Kern	9	Golden Queen Min- ing Co.	Gold ore.
9	Cactus Queen	do Mother Lode	do Amador	13 7	Cactus Mines Co Central Eureka Min-	Do. Do.
1 2		do			ing Co. Miller & Clemson Carson Hill Gold Mining Corpora-	Do. Do.
3	Alabama	Ophir	Placer	12	tion. Alabama California Gold Mines Co.	Do.
4	Original Sixteen to	Alleghany	Sierra	17	Original Sixteen to One Mine, Inc.	
5	One. Placer Properties	Knights Ferry	Stanislaus	31	Placer Properties Co	
6	Co. Snelling	Snelling	Merced	16	Snelling Gold Dredg- ing Co.	Dredge.
7	Dredge No. 4	La Grange	Stanislaus	30	La Grange Gold Dredging Co.	Do.
18	Argonaut Siskiyou Unit	Mother Lode Callahan	Amador Siskiyou	11 126	Argonaut Mining Co Yuba Consolidated Gold Fields.	Gold ore. Dredge.
20	Junction City	Junction City	Trinity	33	Junction City Min- ing Co.	Do.
21 22 23	dredge. Surcease Carr ranch Mount Gaines	Yankee Hill Trinity Center Mother Lode	Butte Trinity Mariposa	29	Hoefling BrosCarrville Gold Co Mount Gaines Mining Co.	Gold ore. Dredge. Gold ore.
24	Cosumnes dredge	Cosumnes River	San Joaquin	32	Cosumnes Gold	Dredge.
25	Kister property	Oroville	Butte	43	Dredging Co. Gold Hill Dredging Co.	Do.

<sup>1</sup> Corrected figure.

Silver.—Most of the silver output in California in 1942 was more localized than that of the gold; the 10 leading silver-producing mines, listed in the following table, yielded 85 percent of the State total recoverable silver in that year. The list is similar to that of 1941, except for some changes in rank and the displacement of the Starlight mine (consolidated with its neighbor), Walker, and Grigsby mines, which suspended operations in 1941. By December, 6 of the 10 leading silver mines had suspended operations.

Ten leading silver-producing mines in California in 1942, in order of output-

Rank	Mine	District	County	Rank in 1941	Operator	Source of silver
1	Cactus Queen	Mojave	Kern	1	Cactus Mines Co	Gold-silver ore.
- 2		Grass Valley-Ne- vada City.	Nevada	Ž	Lava Cap Gold Min- ing Corporation.	Gold ore.
3 4	Columbia No. 2 Golden Queen	Resting Springs Mojave	Inyo Kern	6 3	Shoshone Mines, Inc. Golden Queen Mining	Lead ore Gold ore.
5	Pine Creek	Bishop Creek	Inyo	19	Co. United States Vana- dium Corporation.	Tungsten-mo- lybdenum-
6	Essex-Columbia (Darwin Lead).	Coso	do	16	Imperial Metals, Inc.	copper ore. Silver ore and
. 7	Kelly	Randsburg	San Bernar- dino.	7	Frank W. Royer	lead ore. Silver ore.
8	Empire Star mines_	Grass Valley-Ne- vada City.	Nevada	8	Empire Star Mines	Gold ore.
9	Alabama	Ophir	Placer	9	Co., Ltd. Alabama California	Do.
10	Idaho Maryland- Brunswick.	Grass Valley-Ne- vada City.	Nevada	17	Gold Mines Co. Idahol Maryland Mines Corporation.	Do.

Copper.—Copper production in California was small in 1942 because the Walker mine in the Genesee district of Plumas County, which had contributed over 92 percent of the State copper in 1941, was inactive. The leading copper producer for 1942 was the Pine




FIGURE 2.—Percentage of total California gold produced at lode and placer mines and by various methods of placer mining, 1850–1942.

Creek mine of the United States Vanadium Corporation, in the Bishop Creek district of Inyo County, where copper concentrate was recovered as a byproduct from ore worked principally for tungsten. In October, however, the Keystone Copper Co. made an initial shipment of copper concentrate from Copperopolis in Calaveras County; by the end of the year, the company attained the highest production rate of any mine in the State. Development work at copper proper-

ties was carried on by the Gray Eagle Copper Co. near Happy Camp in Siskiyou County, where a 550-ton plant was under construction, and by the Mountain Copper Co., Ltd., near Kennett in Shasta County,

with a 350-ton plant under construction.

Lead.—The expansion in California's lead production from 990,000 pounds in 1938 to 10,302,000 pounds in 1942 resulted in lead displacing copper as the third most valuable of the five metals produced in the State. The Shoshone Mines, Inc., operator of the Columbia No. 2 mine, was the leading producer, and the Imperial Metals, Inc., operator of a group of mines at Darwin, was the second-largest lead producer; both operations are in Inyo County.

Zinc.—Zinc production in California, although still very small, continued to expand for the fourth successive year. The Combined Metals Reduction Co., operator of the Colorado group in the Modoc district of Inyo County, and W. F. Huston, operator of the Carbonate King mine in the Ivanpah district of San Bernardino County, con-

tributed 77 percent of the State total.

## MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in California in 1942, by counties, in terms of recovered metals

	Mine	s pro-			<u> </u>	Gold		
County	due	ing 1	]	Lođe	P	lacer	To	otal
	Lode	Placer	Fine ounces	Value	Fine ounces	Value	Fine ounces	Value
Alpine	2		17	\$595			17	\$59!
Amador	14	25	39, 418	1, 379, 630	10, 056	\$351,960	49, 474	1, 731, 590
Butte	3	33	7, 363	257, 705	53, 553	1, 874, 355	60, 916	2, 132, 060
Calaveras	23	27	16, 638	582, 330	11, 366	397, 810	28, 004	980, 14
Del Norte		l ~i	10,000	302, 500	11,000	175	20,001	17
Eldorado	22	26	6, 145	215, 075	12,049	421, 715	18, 194	636, 79
resno	- 22	6	0, 140	210,070	1, 166	40.810	1, 166	40, 81
Tumboldt	2	6	3	105	4,020	140, 700	4, 023	140, 80
mperial		1	126	4, 410	4,020	1,680	174	6,09
nyo					7			409, 85
	42	1	11, 703	409,605		245	11,710	
Cern	58 8	7	56, 554	1, 979, 390	360	12,600	56, 914	1, 991, 99
os Angeles		4	356	12, 400	123	4, 305	479	16, 76
Aadera	5	16	27	945	690	24, 150	717	25,09
Aariposa	42	14	20, 503	717, 605	8, 789	307, 615	29, 292	1,025,22
Merced		6			20,053	701, 855	20, 053	701, 85
Iono	11	1	1,831	64, 085	2	70	1, 833	64, 15
Tevada	14	17	154, 927	5, 422, 445	6,666	233, 310	161, 593	5, 655, 75
range	2		5	175			5	17
lacer	10	36	14, 929	522, 515	8, 362	292, 670	23, 291	815, 18
lumas	9	12	6, 867	240, 345	1, 298	45, 430	8, 165	285,77
Riverside	8	2	337	11, 795	11	385	. 348	12, 18
acramento	2	15	6	210	125, 114	4, 378, 990	125, 120	4, 379, 20
an Bernardino	44	5	9,640	337, 400	25	875	9,665	338, 27
an Diego	3		7	245			7	24
an Francisco		(E)			4	140	4	14
an Joaquin		`10			18, 103	633, 605	18, 103	633, 60
an Luis Obispo		ĩ			4	140	4	14
anta Barbara and		•			-		•	
Shasta 3	18	16	4, 192	146, 720	17, 347	607, 145	21, 539	753, 86
ierra	13	31	11, 787	412, 545	6, 243	218, 505	18,030	631, 05
iskiyou	29	49	1,073	37, 555	37, 685	1, 318, 975	38, 758	1, 356, 59
tanislaus	20	5	1,010	37,000	27, 795	972, 825	27, 795	972, 82
rinity	16	38	740	25, 900				846, 89
'ulare		- 30			23, 457	820 <b>, 99</b> 5	24, 197	
Cuòlumne	4 24	7	134 11, 739	4,690	094	20.000	134	4,69
ubia				410, 865	934	32,690	12,673	443, 55
Lung	2	10	6,004	210, 140	69, 591	2, 435, 685	75, 595	2, 645, 82
•	404	400	000 071	10 405 405	404 000	10 070 410	045 005	00 000 00
Datal 1041	434	428	383, 071	13, 407, 485	464, 926	16, 272, 410	847, 997	29, 679, 89
l'otal, 1941	835	724	690, 780	24, 177, 300	718, 013	25, 130, 455	1, 408, 793	49, 307, 75

Mine production of gold, silver, copper, lead, and zinc in California in 1942, by counties, in terms of recovered metals—Continued

era e ere anazio ej. Elemento					<u> </u>		Silve	er			<u> </u>	
County			Lo	de			Plac	er			Tot	al
		Fine		.Va	lue	Fi	ne ices	7	7alue		rine inces	Value
Alpine			3		\$2						3	\$
Amador Butte Calaveras		15,	831 999 214	1	6, 991 1, 377 5, 130		1, 260 4, 351 1, 166		\$896 3, 094 829		11, 091 20, 350 8, 380	7, 88 14, 47 5, 95
Del Norte			647		460		1, 637		1, 164		2, 284	1,62
resno Iumboldt mperial			14 169		10 120		201 623		143 443		201 637 169	14 45 12
nyo Kern		333, 597,	367 614		7, 061 4, 970		69		1 49		333, 368 597, 683	237, 06 425, 01
os Angeles		7.	208 52 875		148 37 5, 600		21 190 1,744		15 135 1, 240		229 242 9, 619	16 17 6, 84
Merced Mono		15,	580	1	1,079		1,942		1,381		1, 942 15, 581 300, 963	1, 38 11, 08
Vevada Drange Placer		300, 3, 30,	323 517		3, 504 2, 363 21, 701		723		707		3, 323 31, 511	214, 01 2, 36 22, 40
Plumas Riverside Sacramento			838 180 1		596 128 1		121 6, 386	e j	86 1 4, 541		959 181 6, 387	68 15 4, 5
an Bernardinosan Diegosan Francisco		65,	717 3	4	6, 732 2				-, 011		65, 717	46, 7
an Joaquin							1, 762		1, 253		1, 762	1, 2
an Luis Obispo anta Barbara and Shasta ierra		2.	195 129 315		9, 383 1, 514 224		2,001 502 5,573		1, 423 357 3, 963		15, 196 2, 631 5, 888	10, 80 1, 81 4, 10
iskiyou tanislaus Trinity			308		219		2, 544 2, 506		1, 809 1, 782	* :	2, 544 2, 814	1, 80 2, 00
Tulare Tuolumne Tuba		3,	57 538 871		2, 516 619		83 4, 230		59 3, 008		57 3, 621 5, 101	2, 5° 3, 6°
Fotal, 1941	-	1, 409, 805 2, 088, 713		1, 409, 805 2, 088, 713 1, 40		40, 635 65, 475			28, 896 46, 560	1, 450, 440 2, 154, 188		1, 031, 42 1, 531, 86
		Copper		er		Lead		Zinc			motal.	
County	P	ounds	v	alue	Pou	ınds	Value	•	Pounds	T	Value	Total value
Alpine		4,000		\$484		2,000	\$1	 34				\$5 1, 740, 0
Butte Calaveras		532,000		4, 372					8,000		\$744	2, 146, 5 1, 051, 2
Del Norte Eldorado Fresno		2,000		242				 		-		638, 6 40, 9
Iumboldt mperial nyo		6,000 740,000		726 9, 540	10.17	0,000	681, 3		754, 000	-	70, 122	141, 9 6, 2 1 487 9
Kern Los Angeles		2,000		242		8,000	5	36	754,000			1, 487, 9 2, 417, 7 16, 9
Aadera		66, 000 18, 000		7, 986 2, 178	i	6, 000	1,0	72				33, 2 1, 035, 3 703, 2
Mono Vevada		14, 000		1, 694	i	4,000	9	38	6.000		558	75, 2 5, 872, 4 3, 3
Placer Plumas		6,000		726	2	4,000 24,000 2,000	1,6	68 08 34	6,000	<u>.</u>		839, 9 286, 5
Riverside acramento an Bernardino		2,000 154,000	;	242 8, 634		 50, 000	4,0		458,000		42, 594	12, 8 4, 383, 7 450, 2
San Diego San Francisco									250,000			1
San Joaquin San Luis Obispo				·						-		634, 8

See footnotes at end of table.

Mine production of gold, silver, copper, lead, and zinc in California in 1942, by counties, in terms of recovered metals—Continued

	Copp	oer	Lea	ıd	Zi	Total	
County	Pounds	Value	Pounds	Value	Pounds	Value	value
Santa Barbara and Shasta 3	562, 000	\$68,002	2,000	\$134			\$832, 807 632, 921
Sierra Siskiyou Stanislaus	4,000	484					1, 361, 201 974, 634 848, 896
TrinityTulareTuolumneYuba	4,000	484					4, 731 446, 614 2, 649, 452
Total, 1941	2, 116, 000 7, 886, 000	256, 036 930, 548	10, 302, 000 6, 928, 000	690, 234 394, 896	1, 226, 000 880, 000	\$114, 018 66, 000	31, 771, 607 52, 231, 066

<sup>&</sup>lt;sup>1</sup> Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to property.

property.

2 Output from property not classed as a "mine."

3 Combined to avoid disclosure of individual output.

## MINING INDUSTRY

The tonnage of material from lode mines in California treated in 1942 decreased 42 percent compared with 1941, and the yardage at placer mines decreased 29 percent; the output of lode gold declined 45 percent and that of placer gold 35 percent. The average recoverable gold content of gravels declined 8 percent. Of the State total gold output in 1942, 45 percent was from lode mines and 55 percent from placers; this represented the highest placer: lode ratio since 1900, when separate annual data were first compiled, and almost certainly the highest since large-scale hydraulicking was terminated by the Sawyer Decision of 1884.

Dredges of the connected-bucket type washed 78 percent of the gravel mined and recovered 67 percent of the State total placer gold in 1942.

Dragline dredging, which had had such a spectacular rise during the years following its inception in California in 1933, reacted most unfavorably to war conditions; gold production by this method decreased 48 percent. The great demand for dragline excavators and for labor skilled in earth-moving caused rapid abandonment of dragline-dredge operations. The following table gives partial data on equipment in the dragline industry over a 4-year period; information on bucket size was supplied for 52 dredges in 1939, 89 in 1940, 94 in 1941, and 72 in 1942.

Size of buckets		Number	of boats	3	Size of buckets	Number of boats				
(cubic yards)	1939	1 <b>94</b> 0	1941	1942	(cubic yards)	cubic yards)	1941	1942		
7½ 6 5 4	1	1 2 1	2 6	1 7	134 114 114 1	2 17 5 4	3 25 9 9	8 19 6 6	1	
31/4 3	1 3 4 2 10	4 8 1 15	5 19 1 13	7 12 1 9	%	1 2	7 3 1	8		

Other placer-mining methods all showed decreases in quantity of gravel washed and gold recovered. The only gold credited to the Becker-Hopkins type of dredging resulted from the clean-up of a dredge, which suspended operations in 1941. Nonfloating washing plants to which gravel was delivered by mechanical means (dragline excavators, power shovels, slackline excavators, trucks, bulldozers) treated much less gravel in 1942 than in 1941. Many of these operators found that their equipment could be employed more profitably on war contracts; competition for labor skilled in operating earthmoving machines was very keen.

Suction dredging, which to date in California has been confined almost entirely to Fresno and Madera Counties, seemed to be expanding early in 1942, but by the end of the year these operations were largely suspended. The prospect that new techniques developed in relatively small scale suction dredging would be applied more widely

左右 ないこうないことになって

in California after the war seemed favorable.

Hydraulic mining at established mines found itself singularly free from shortages of materials and power, but labor conditions caused marked reductions in operations. Very few hydraulic mines reopened for the 1942–43 season. Gold production from small-scale hand methods was sharply curtailed. In normal times, a large number of such operations are carried on independently by marginal workers, but the increasing labor shortage in California in 1942 caused many small-scale hand miners to abandon the streams and dry diggings for employment at wages. Drift mining, once very productive in California, also declined owing to war conditions.

Consumption of quicksilver at California placer mines totaled 13,944 pounds in 1942 compared with 19,949 pounds in 1941. The following quantities of gold were recovered to the pound of quicksilver used in 1942 (1941 figures in parentheses): Connected-bucket dredging, 34 ounces (40); dragline dredging, 40 ounces (37); suction dredging, 15 ounces (13); nonfloating washing plants with mechanical gravel handling, 17 ounces (42); hydraulicking, 16 ounces (22); small-scale hand operation, 18 ounces (15); and drift mining, 146 ounces (72).

#### ORE CLASSIFICATION

Of the 2,503,198 tons of ore (including 625,564 tons of old tailings) sold or treated in 1942, 82 percent was dry gold ore and old tailings, 16 percent copper ore (including a large quantity of ore valued more for its tungsten and molybdenum than copper), 1 percent lead ore, and most of the remainder dry silver ore.

Details of ore classification are given in the chapter of this volume on

Gold and Silver.

The second of th

Ore and old tailings sold or treated in California in 1942, with content in terms of recovered metals

	Material trea						
Source	Ore	Old tailings	Gold	Silver	Copper	Lead	Zine
Dry and siliceous gold ore Dry and siliceous gold-	Short tons 1,437,480	Short tons 625, 119	Fine ounces 377, 249	1,008,308	189, 500	Pounds 66, 200	Pounds
Silver ore Dry and siliceous silver ore_	621 12, 886	445	168 285	8, 597 69, 342	3,700 4,500	594,000	6,000
Copper ore 1 Lead ore Zinc ore Zinc-lead ore	1, 450, 987 393, 944 29, 857 5 2, 089 752	625, 564	377, 702 436 4, 916 3 9 5	1, 086, 247 71, 175 248, 240 301 2, 304 1, 538	194,700 2 1,898,800 20,100 300 1,000 1,100	660, 800 6, 600 9, 454, 400 1, 600 47, 200 131, 400	957, 000 263, 000
Total, lode mines Total, placers	1,877,634	625, 564	383, 071 464, 926	1, 409, 805 40, 635	<sup>2</sup> 2, 116, 000	10, 302, 000	1, 226, 000
Total, 1941	1, 877, 634 3, 435, 109	625, 564 845, 076	847, 997 3 1,408, 793	1, 450, 440 3 2,154, 188	<sup>2</sup> 2, 116, 000 <sup>3</sup> 7, 886, 000	10, 302, 000 6, 928, 000	1, 226, 000 880, 000

Includes ore valued principally for tungsten and molybdenum.
 Includes 71,100 pounds from precipitates.
 Includes metals recovered from tungsten ore.

#### METALLURGIC INDUSTRY

During 1942, as in former years, most of the ore and virtually all the old tailings were treated at amalgamation and cyanidation mills (with or without concentrating equipment); 80 percent of the total ore and old tailings was treated at such mills in 1942. Almost all the remaining ore was treated at concentrating mills; only 60,395 tons of crude ore were shipped for direct smelting. Smelters also received 21,314 tons of flotation concentrates and 288 tons of gravity concentrates from California mine operators. Comparing 1942 with 1941, material treated at amalgamation mills decreased 63 percent, material treated at cyanidation mills decreased 55 percent, and quantity of crude ore and old tailings smelted increased 35 percent; the quantities of ore concentrated in 1941 and 1942 are not comparable because a substantial quantity of tungsten ore was included in the latter year and excluded in the former.

Quicksilver consumption at California amalgamation mills totaled 3,040 pounds, used in the treatment of 785,945 tons of material to recover 144,004 ounces of gold and 29,010 ounces of silver in 1942. In the treatment of 503,551 tons of ore, 135,896 tons of old tailings, and 5,918 tons of concentrates to recover 106,092 ounces of gold and 344,476 ounces of silver, cyanide consumption was 110,701 pounds of 91-percent sodium cyanide and 744,246 pounds of commercial calcium cyanide (50-percent NaCN equivalent); in terms of 98-percent NaCN, the consumption was 467,475 pounds or 0.72 pound to the A substantial part of the cyanide was consumed at custom mills in California.

Companies producing most of California's lode gold in 1942 owned and operated their own metallurgical plants, but a number of custom mills were active. The leading operators of metallurgical plants receiving custom material were: Burton Bros., Inc., Rosamond, Kern County; Golden Queen Mining Co., Mojave, Kern County; Mineral Reduction Co., Benton, Mono County; and F. W. Royer, Red Mountain, San Bernardino County. All these mills were cyanidation plants

and accepted ore and old tailings for treatment. The Idaho Maryland Mines Corporation and Empire Star Mines Co., Ltd., Grass Valley, Nevada County, cyanided some lots of concentrates. The zinc oxide plant of the Pacific Zinc Oxide Co. (formerly Western Zinc Oxide Co.), Richmond, Contra Costa County, which had treated oxidized zinc ores in 1941, suspended operations early in 1942. The largest metallurgical custom plant in California—the Selby lead plant of the American Smelting & Refining Co. at Selby, Contra Costa County—continued to be the State's only smelter. By the end of the year, all these custom plants except the Selby smelter had suspended operations.

Mine production of metals in California in 1942, by methods of recovery, in terms of recovered metals

Method of recovery	Material treated	Gold	Silver	Copper	Lead	Zinc
Ore, old tailings, and concentrates amalgamated	Short tons 785, 945	Fine ounces 144, 004	Fine ounces 29,010	Pounds	Pounds	Pounds
Ore, old tailings, sands, slimes, and concentrates cyanided Concentrates smelted:	1,006,361	133, 710	395, 350			
Flotation	21, 314 288	89, 818 2, 168	657, 374 2, 041	1, 284, 200 100	713,300	547, 000
Ore and old tailings smelted Precipitates	60, 395	13, 371	326, 030	760, 600 71, 100	9, 588, 600	679,000
Total, lode mines		383, 071 464, 926	1, 409, 805 40, 635	2, 116, 000	10, 302, 000	1, 226, 000
Total, 1941		847, 997 1, 408, 793	1, 450, 440 2, 154, 188	2, 116, 000 7, 886, 000	10, 302, 000 6, 928, 000	1, 226, 000 880, 000

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in California in 1942, by types of mills and by counties, in terms of recovered metals

AMALGAMATION MILLS

	Material	treated	Recov	ered in lion	Concen	trates sme	elted and	recoveréd	l metal
County	Ore 1	Old tail- ings	Gold	Silver	Concen- trates produced	Gold	Silver	Copper	Lead
Alpine	Short tons	Short tons	Fine ounces 17	Fine ounces	Short tons	Fine ounces	Fine ounces	Pounds	Pounds
AmadorButte	88, 201 76		24, 038 720	4, 954 90	1,311	5, 086 13	753 2	2,000	1,800
Calaveras Eldorado Imperial	7, 557 4, 533 188	400	6, 603 2, 701 124	956 295 143	960 1, 325	4, 548 3, 165	2,709 221	2, 500 2, 000	
Inyo Kern Los Angeles Madera	981 20, 573 1, 187	2, 450	176 1,945 98 8	317 809 22 3	354 14	1, 325 39	4, 585 24	300	6, 900
Mariposa Mono			7, 573 26	1,871 26	1,609	10, 709	3,829	2,000	16,000
Nevada	291, 225 64, 935 702		67, 280	12, 085 4, 045 21 16	1 496	33 2, 149	25, 919	100 3, 500	23, 400
San Bernardino	4.170		6 390	1 63	1	7	2		
San Diego Shasta Sierra	6, 941 26, 811	5, 800	1,709 11,283	3 400 1,977	323 127	1, 259 504	299 152		
Siskiyou Trinity Tulare	2, 522 6, 174 363	8	1,039 529 65	294 107 29	2 25 21	10 59 69	5 18 28		
Tuolumne Yuba			942 4, 404	209 271	3, 872	10, 756	3, 286	4,000	
Total, 1941	777, 287 2, 102, 150	8, 658 2, 148	144, 004 285, 038	29, 010 65, 978	10, 445 14, 666	39, 731 115, 466	41, 839 401, 151	16, 500 64, 800	48, 100 102, 000

See footnotes at end of table.

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in California in 1942, by types of mills and by counties, in terms of recovered metals-Continued.

#### CYANIDATION MILLS

			1 1111111111111111111111111111111111111	LIIOIV I	VIII)))				9
	Materia	l treated		ered in llion	Concen	trates sme	elted and	recovered	metal
County	Ore 1	Old tail- ings	Gold	Silver	Concen- trates produced	Gold	Silver	Copper	Lead
Amador	Short tons 18, 688 27, 480	Short tons 133, 756	Fine ounces 9, 711 6, 630	Fine ounces 3, 847 15, 907	Short tons	Fine ounces	Fine ounces	Pounds	
Calaveras Eldorado Inyo Kern Los Angeles	144, 954 514 24, 997 128, 000 602	280 301, 080	5, 242 154 6, 005 39, 473 216	2, 400 67 3, 181 295, 248 144	4 194	175 13, 805	91 296, 961	1,700	100 1, 100
Mariposa Mono Nevada Placer	21, 471 168, 682 153	1, 745	99 1, 805 56, 710	61 15, 443 54, 483	4, 912	30, 804	233, 130	13, 200	12, 000
Plumas Riverside San Bernardino	13, 392 228 7, 743	445	543 2, 331 275 2, 042	238 59 150 2,836	23	171 203	50 548		2, 000
San Diego Shasta Siskiyou Yuba	11,050 1,000	100	863 8 1,600	685 1 600					
Total, 1941	568, 955 1, 382, 119	437, 406 842, 983	133, 710 232, 695	395, 350 771, 977	5, 150 361	45, 158 16, 234	530, 780 319, 900	14, 900 2, 300	15, 200 5, 500
Grand total: 1942 1941	1, 346, 242 3, 484, 269	446, 064 845, 131	277, 714 517, 733	424, 360 837, 955	15, 595 15, 027	84, 889 131, 700	572, 619 721, 051	31, 400 67, 100	63, 300 107, 500

<sup>&</sup>lt;sup>1</sup> Figures under "Ore" include both raw ore and concentrates amalgamated or cyanided, but not raw ore concentrated before amalgamation or cyanidation of concentrates.

## Mine production of metals from concentrating mills in California in 1942, by counties, in terms of recovered metals

				Concentr	ates smelte	ed and recove	ered metal	
	County	Ore	Concen- trates produced	Gold	Silver	Copper	Lead	Zine
Calaveras Eldorado Inyo Mariposa Nevada Orange Placer Plumas Trinity Tuolumne		Short tons 13, 107 350 1 390, 973 4, 916 200 100 80 25, 376 100	Short tons 1, 682 35 2, 747 277 40 12 21 1, 179 4 10	Fine ounces 237 106 245 2, 107 45 2 10 4, 221 84 40	Fine ounces 987 41 82, 126 1, 711 348 550 140 696 156 41	Pounds 528, 200 721, 900 700 2, 100	Pounds 646, 100 2, 000 2, 000	Pounds 8, 000 533, 000 6, 000
Total, 194	1	435, 332 392, 406	6,007 19,593	7, 097 2 26, 013	86, 796 2 240, 288	1, 252, 900 2 7, 520, 300	650, 100 95, 000	547, 000 183, 300

#### Gross metal content of concentrates produced from ores mined in California in 1942, by classes of concentrates

	Concen-	Gross metal content							
Class of concentrates	trates	Gold	Silver	Copper	Lead	Zinc			
Dry gold	Short tons 17,020 195 2,981 1,294	Fine ounces 78, 212 13, 600 111 62 1	Fine ounces 279, 036 296, 982 57, 944 25, 092 361	Pounds 51, 282 3, 633 1, 285, 549 106 375	Pounds 76, 277 816 6, 392 668, 029 4, 061	Pounds 1,877 51,286 608,429			
Total, 1941	21, 602 34, 620	91, 986 157, 713	659, 415 961, 339	1, 340, 945 7, 863, 822	755, 575 239, 878	661, 592 237, 122			

Includes ore valued principally for tungsten and molybdenum.
 Includes concentrates and metals from tungsten ore not included in material treated.

Mine production of metals from California concentrates shipped to smelters in 1942, in terms of recovered metals

## BY COUNTIES

	Concen- trates	Gold	Silver	Copper	Lead	Zinc
	Short tons		Fine ounces	Pounds	Pounds	Pounds
Lmador	1,311	5, 086 13	753	2,000	1,800	
Butte		4, 785	3,696	530, 700		8,000
Eldorado		3, 271	262	2,000		0,000
nyo.		420	82, 217	721, 900	646, 200	533, 000
Cern		15, 130	301, 546	2,000	8,000	
os Angeles	14	39	24			
Mariposa.		12,816	5, 540	2,000	16,000	
Tevada		30,882	233, 485	14,000	14,000	
)range	12	2	550		2,000	6,000
lacer	517	2, 159	26,059	5,600	23, 400	
lumas.	1,202	4, 392	746		2,000	
an Bernardino	18	210	550			
hasta		1,259	299	100		
ierra		504	152			
iskiyou		10	5			
Prinity		143 69	174 28			
Fulare		10,796	3, 327	4,000		
Tuolumno	3,882	10, 796	3, 341	4,000		
	21, 602	91, 986	659, 415	1, 284, 300	713, 400	547,000
Γotal, 1941	34, 620	157, 713	961, 339	7, 587, 400	202, 500	183, 300
	BY CLASS1		CENTRAT 279, 036	ES 30, 500	64, 900	
Dry gold Dry gold-silver		13, 600	296, 982	2,400	700	
Copper	2,981	111	57, 944	1, 251, 100	3,800	
Jopper Lead		62	25, 092	-, 202, 200	640, 300	
Zinc	112	1 1	361	300	3,700	547,00
<del></del>			0.50 15 -	1 004 000	P10 400	F4F 00
	21,602	91, 986	659, 415	1, 284, 300	713, 400	547,00

Gross metal content of California crude ore shipped to smelters in 1942, by classes of ore

	Materia	shipped	Gross metal content					
Class of ore	Ore	Old tail- ings	Gold	Silver	Copper	Lead	Zinc	
Dry gold Dry gold-silver Dry silver Copper Lead Lead-copper Zine Zine- Z	Short tons 23, 907 139 1, 334 3, 736 29, 857 749 668	Short tons	Fine ounces 7,865 20 226 335 4,916 3 1 5	Fine ounces 17, 522 635 44, 242 13, 371 247, 931 301 543 1, 485	Pounds 169, 877 4, 261 2, 385 1 669, 430 24, 998 523 61 1, 296	Pounds 1, 505 670 5, 887 4, 183 9, 862, 383 1, 761 16, 745 151, 218	Pounds	
Total, 1941	60, 395 44, 810	9	13, 371 15, 334	326, 030 289, 419	<sup>1</sup> 872, 831 335, 534	10, 044, 352 7, 009, 914	3, 702, 336 773, 84	

Includes 71,445 pounds contained in precipitates.

Mine production of metals from California crude ore shipped to smelters in 1942, in terms of recovered metals

## BY COUNTIES

	Material	shipped					
		Old tail-	Gold	Silver .	Copper	Lead	Zinc
	Ore			100		4	
		ings	11.71				1 1 2
	~• .	~ .	77'	775		7	
	Short	Short	Fine	Fine ounces	Pounds	Pounds	Pounds
	tons	tons	ounces		2,000	200	1 Utilities
mador	220		583	277 162	1, 300		
alaveras	49		8		1,500		
ldorado	39		19	23			
[umboldt	41		3	14	6,000		
mperial	22		2	26			
170	30, 329		5, 102	247, 652	18, 100	9, 523, 800	221,000
ern	5		6	11			
os Angeles	ğ		3	18			
Iadera	26		19	49	1 66, 000		
Iariposa	144		15	403	16,000		
	1		10	111	25,000		
ono	42		55	187			
evada			3	2, 773		2,000	
ange	40				400	2,600 600	
acer	60		52	175	400	1900	
umas	3		40	12			
verside	45		17	14	2,000		
n Bernardino	23, 761		6, 998	62, 268	154,000	60,000	458,000
n Bernardino nta Barbara and Shasta 2	5, 483	l	361	11, 811	3 561, 900	2,000	
skivou	48		16	15	4,000		
rinity	12		68	27	L		
uolumne	16		l ~~~	2	1		
Olumne							
	60, 395		13, 371	326, 030	4 831, 700	9, 588, 600	679, 000 696, 700
tal, 1941	44, 810	9	15, 334	289, 419	298, 600	6, 725, 500	080, 700
	В	Y CLASS	ES OF O	RE			
Ory gold	23, 907		*7,865	17, 522	154, 700	600	
Aly gold officer	139		20	635	3,700	600	
Ory gold-silver Ory silver	1, 334		226	44, 242	1, 500	4, 500	
ory suver	3, 736		335	13, 371	4 649, 800	2,800	
Copper	0, 100		4, 916	247, 931	20,600	9, 454, 400	
ead	29, 857		4, 910	301	300	1, 600	
ead-copper	5				ano	12, 100	458, 00
	749	I	1	543	1, 100	112, 100	221,00
inc							
ac	668		5	1, 485	1, 100	112,000	221,00

Includes 60,000 pounds from precipitates.
 Combined to avoid disclosure of individual output.
 Includes 11,100 pounds from precipitates.
 Includes 71,100 pounds from precipitates.

# REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, lead, and zinc in California in 1942, by counties and districts, in terms of recovered metals 1

County and district 1	Mines ir	produc- ig <sup>2</sup>	Ore and old tailings		Gold		Silver (lode	Copper	Lead	Zine	Total value
	Lode	Placer	Lamings	Lode	Placer	Total	and placer)3	Copper	Dead	Ziiii	Total value
Alpine County: Monitor	-		Short tons 58	Fine ounces		Fine ounces	Fine ounces	Pounds	Pounds	Pounds	\$597
Camanche <sup>3</sup> East Belt <sup>5</sup> Ione Lancha Plana	5	3	2,748	2, 995	137 1, 133 2, 581 227	137 4, 128 2, 581	14 1,730 212	2,000	200		4, 805 145, 965 90, 486
Mother Lode 6	. 9	13	400, 837	36, 423	5, 978	42, 401	9, 118	2,000	1,800		7, 957 1, 490, 882
Butte Creek Enterprise Forbestown		1			3, 088 28 50	3, 088 28 50	277 3				
Magalia Merrimac Oroville		(7) 3			■ 134 25	134 25	14 3				
Yankee Hill	2	21 2	27, 484	7, 346	50, 012 216	50, 029 7, 562	4, 015 16, 031				1, 753, 870 276, 070
Campo Seco		5	13, 294	389	805 93	805 93 389	52 28 1, 059	527, 200			
East Belt 6	9	2 4 15	6, 247 700	2, 271 862	152 5, 232	2, 423 6, 094	322 962	500 <b>2</b> 00			85, 095
West Belt 9 Del Norte County: French Hill	i	15	194, 743 106	13, 108 8	5, 084	18, 192 8 5	5, 569 388 3	1, 800 2, 300			640, 898 1, 578 177
Eldorado County: East Belt  Mother Lode 6 West Belt 9	16	4 17 5	950 36, 403 442	139 5, 853 153	2, 516 7, 494	2, 655 13, 347	550 1,487	2,000			93, 316 468, 444
Fresno County: Auberry Friant		(7)	442	103	2,039	2, 192	247 7				76, 896 950
Humboldt County: China Flat		1			1, 139	1,139	194				40,003
Gold Bluff Orleans Imperial County:	2	1 4	41	3	3, 999	18 4,002	634	6,000			632 141, 247
Cargo Muchacho Mesquite Diggings Picacho	3	(7)	209	14 112	8 20 19	22 132 19	7 162				
Pot Holes		1 , 1			1	1 19					665 35

CONTRACTOR OF THE PROPERTY OF

する 一般の 大きな 一般の 一般の 一般の 一般の はない なっという こうしゅうしゅう

		G	OL	D,	SIL	VE	R,	CC	PI	E.	к,	L	E.A	LD	, A	N.	D	ZL	NC	1	N	C	VL.	LFO	)RI	NIZ	7
•	20, 935 4, 703	412 145 446	462	55, 056 860, 320	130, 474 21, 908	34,835 1,599	32, 709 47, 344	785	8, 957	492	7, 651	847 9. 937	35	2, 047, 011	260,842	460 495	2 940		6.584	4, 320	1,725	9, 506 247	13, 089	105, 535	282, 806 646, 969	1.055	1,300 700,881
	159,000			491,000	1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	104,000								-													
	71,400 300	1,510,900	1,600	88, 500 8, 088, 000	300 245, 100	8,800 8,900	100		6.900					1, 100										1	16,000		
	1, 100	2 900	300	13,000	200				300					1,700							1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1				16,000 2,000		
	107 1, 485 138	53.072	Î	2, 210 210, 503	ଔ	ณ์	ณ์		4.640	6	128	10		589, 839	2,935	- 2-	48	1	153	21	11	<u>~</u>	26		3, 537 5, 576	4	1,928
	131	112	100	4,776	3,725	25.53	1, 333	23	255		216	42.8	3-	46, 494	7, 393	14	149	8	185	123	49	272	372	3,002	18, 334	30	19, 986
			7					1	255	10	OT	63	1-	1	91					123	49	0/2	371		3, 080	30	19, 986
	131	111	က	53 4, 776		88	1,333	22	2, 325	14	216	84∞		46, 494	7, 302	5 T	149	8	185			7	-	2,968	2,281 15,254		
-	23 23 23 23 23 23 23 23 23 23 23 23 23 2	15.028		1,466 25,001		2,319	2, 781		16. 467	16	401	216		126, 982	307, 686	71-0	950	317	228			9	-	4, 566	7, 229 81, 840		1
			-						-	(	2	r-1 r-		-	က					4	en c	8	10	-	<b>6</b> 1~	-	
	0	ı —ı ec	-	60	ကက္	200	CJ 4	4	1	-	9	CJ 4	'	22.0	<b>'.</b> a'		67	· ·	- 60			2	7	13	3° 8		
A:	ma Hills. Gordo ide Cliff	dence	Springs.	oo ng Springs	nan Range	Park 6be	Rose	inty: ie	a Grade	er Mountain	Mountain	ah	Tom	Ve	Isburg 10	River 11	es County:	Mountain	ach	labriel	chilla River 18	oth.	r Ridge	Belt 4	er Valley 18	ounty: chilla River 12	er Valley 13 ng

See footnotes at end of table.

Mine production of gold, silver, copper, lead, and zinc in California in 1942, by counties and districts, in terms of recovered metals 1—Continued

Zinc Total value		\$352 652 652 652 652 752 752 752 752 752 752 752 752 752 7	11, 337 11, 337 140 140
Mines produce if Gold Silver Gode Copper Lead Z		Pounds P 12,000 2,000 600 600 23,400	
Copper		Pounds 13, 200 800 800 6, 600	1,600
Silver (lode	and placer).	Fine ounces 4394 4394 4394 119 119 119 119 119 119 119 119 119 1	3 174 3
	Total	155,797 155,797 2,072 2,073 2,886 2,886 2,886 2,886 1,0 10,487 10,48	
Gold	Placer	7776 ounces 1, 20, 080 1, 20	04 44 #
	Lode	Fine ounces 12 2 37 153,887 153,887 150 10 10 11 14,716 14,716 2,380 2,380	8 319
Ore and old	ranings	Short tone 38 27 27 27 95 427, 937 427, 937 418 114 14 17 47 47 47 47 47 47 47 47 47 47 47 47 47	305
Mines produc-	Placer	€ € € C C C C C C C C C C C C C C C C C	1 1 8
Mines	Lode	0011 00100 00 H 00 001 00	H 44 HC
County and district 1		Mono County: Blind Springs. Chidago Chidago Chidago Chidago Chidago Chidago Masonic Newada County: French Corral Grass Valloy-Newada City North Bloomfield You Belt Vashington You Belt Orange County: Santa Rosa Placer County: Butcher Ranch Dutch Flat Foresthill I Last Chance Lincoln Michigan Bluff Ophit Plumas County: Genesie Granite Basin Granite Bas	Riverside County: Bardigo. Chuckwalla. Bale Mountain. Eagle Mountain.

100		
'n.	0	
	ð	· ·
٠.,	P	
	D	
	•	
	ZQ.	
	7	
,		
1.	ಸ	
	•	
	0	
	õ	
	ΡĐ	
'	70	
	四	
/	್ವಶಾ	
;	- 31	
	- 5	
	(7)	
5		
5	0	
)	ю,	
	2	
	3	
Į.	Q	
) .	N	
. "	H	
	Z	40.
,	വ	
•	-	4.
<b>.</b>	Z	
2		1
5	ୃΩ	
	15	
3	Н	
7	펼	
3	ည	
)	20	
Ĺ	_ 🖆	
		٠.
	GOLD, SILVER, COPPER, LEAD, AND ZINC IN CALIFORNIA	

acramento County: Cosumnes River. Folsom Walltown.	1	6 9	1 1 1	1 5	15, 909 109, 205	15, 909 109, 206 5	834 5, 552 1			 557, 408 3, 826, 158 176
San Bernardino County: Amargosa. Bellylle. Black Hawk. Buckeye.	1 4 1		11 1, 185 27 18, 103	30 236 54 6,019		30 236 54 6,019	17 187 38 15, 785	44, 500	1,300	 1,062 GOLD 13,865 1,917 238,143
Calico Clark Mountain Coolgardle Dale <sup>14</sup> Holcomb Valley	ll	1	471 372 4, 383	55 1,178	11	55 11 1, 178	2, 904 2, 212 986	2, 100	16, 000	2, 065 4, 824 885 41, 931
Holcomb Valley. Kelso. New York Mountains. Old Woman Mountains. Randsburg <sup>16</sup>	1 8	2	4, 103 35 114 69 3, 905	480 10 1 12 734	11	491 10 1 12 737	509 69 682 509 39, 479	3, 200 1, 100	12, 200	 17,547 E3 399 E3 1,724
Ship Mountain Sliver Mountain Slate Range	1 4		2, 155 62 1 269	505 18 281		505 18 281	266 536 50 291	8,000	7, 000 400 6, 400	 18,832 F 1,480 F 68 E 10,495 F
Vanderbilt. Whitpile Mountains San Diego County: El Cajon. Julian	,		21 16 4 20	17 7 3		17 7 8	34	1,500		626 427 107 35
Pine Valley San Francisco County: San Francisco San Joaquin County: Camanche 4	1	( <sup>7</sup> )	1	3	16, 169	16, 169				 105 140 567, 074
Jenny Lind San Luis Obispo County: La Panza San Luis Obispo County: La Panza Shasta County: French Guich	5	(15) 13		2, 778	1, 934 4 (15) 9, 594	1, 934 4 16 2, 778 9, 594	132 16 616	100		 140 16 97, 680
lgo North Cow Creek Old Diggings Redding Shasta	1	(7) (7) (15)	55 417 145	47 128 59	9, 594 50 75 (18)	9, 594 50 122 16 128 203	928 7 72 16 66 39	100 100		 1,785 4,883 18 4,539
Slate Creek Sierra County: Alleghany Depot Hill		(7) 9 2	50 28, 986	10, 613	888 128	62 11, 301 128	38 21 1,928 10			 2, 185 ALL 396, 906 4, 487
Downleville. Pike. Poker Flat. Sierra City. See footnotes at end of table.	` 3	(7)	(15) 3, 548	(16) 1,056	954 78 404 73	17 954 1, 134 404 78	17 124 294 43 25			17 33, 478 ORNIA 39, 899 14, 171 2, 748

See footnotes at end of table.

Mine production of gold, silver, copper, lead, and zinc in California in 1942, by counties and districts, in terms of recovered metals 1—Continued

County and district 1		produc- g 2	Ore and old		Gold		Silver (lode	Copper	Lead	Zinc	Total value
	Lode	Placer	tailings	Lode	Placer	Total	and placer)3	Сорры	2000		10002 (0.000
Sisklyou County: Callahan Deadwood Gazelle	4 3 1	7 4	Short tons 33 129 10	Fine ounces 44 44 5	Fine ounces 8, 296 2, 246	Fine ounces 8, 340 2, 290 5	Fine ounces 1,042 426	Pounds			\$292, 641 80, 453
Greenhorn Humbug Klamath River Liberty Quartz Valley	7 6 3	(18) 11 12 1	53 140 460 535	21 100 236 189	3, 596 (18) 21, 595 1, 443 42	3, 596 16 21 21, 695 1, 679 231	502 16 3 3, 399 252 73	4,000			58, 944 8, 137
Salmon River. Scott Bar. Stanislaus County: La Grange. Trinity County:	2	3 1 3	1,310	434	174 59 17, 514	174 493 17, 514	28 122 1,561				6, 110 17, 342 614, 100
Big Bar Coffee Creek Crow Creek Hayfork	(15)	1 1 2 3	(15) 4	(15)	165 99 126 811	166 17 99 126 981	17 10 17 10				4,410
Helena Junction City Lewiston New River	1 2 4 1	3 6 6 1	1 137 5, 961 5	11 48 390 3	210 8, 561 2, 481 36	8,609 2,871 39	24 810 353 3				7, 752 301, 891 100, 736 1, 367
Trinity Center. Weaverville. Tulare County: White River 11 Tuolumne County:	1 1 4	(15) 2	100 20 371	84 9 134	(15) 3,727	3, 736 134	16 156 322 57				1, 75 16 3, 05 130, 98 4, 73
East Belt   Mother Lode   West Belt   Yuba County:	7	(7)	285 144, 141 1	331 11, 399 9	120 764 50	451 12, 163 59	97 3, 517 7				15, 854 428, 690 2, 070
Bear River Brown Valley Camptonville Challenge	1	(7)	18, 744	5, 994	120 125 6	120 5,994 125 6	10 871 17				210
Dobbins Smartville Strawberry Valley Other districts <sup>18</sup>		1 3 1 9	90 442, 115	7, 397	39 7, 273 219 90, 878	49 7, 273 219 98, 275	3 540 22 93, 205	19 1, 350, 000		458,000	1, 717 254, 939 7, 681 3, 713, 349
Total California	434	428	2, 503, 198	383, 071	464, 926	847, 997	1, 450, 440	19 2, 116, 000	10, 302, 000	1, 226, 000	31, 771, 607

1 Only those districts shown separately for which Bureau of Mines is at liberty to publish figures; others producing listed in footnote 18 and their output included under "Other districts."

1 Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence

of legal right to property.

\*\*Source of total silver as follows: 1,409,805 ounces from lode mines and 40,635 ounces from placers.

\* Camanche district lies in Amador, Calaveras, and San Joaquin Counties.

- \* East Belt district lies in Amador, Calaveras, Eldorado, Mariposa, and Tuolumne Counties.
- 6 Mother Lode district lies in Amador, Calaveras, Eldorado, Mariposa, and Tuolumne

- 7 Output of property not classed as a "mine."

  3 Jenny Lind district lies in Calaveras and San Joaquin Counties. West Belt district lies in Calaveras, Eldorado, and Tuolumne Counties.

10 Randsburg district lies in Kern and San Bernardino Counties.

- 11 White River district lies in Kern and Tulare Counties.
- 12 Chowchilla River district lies in Madera and Merced Counties.
  13 Hunter Valley district lies in Mariposa and Merced Counties.
- Dale district lies in Riverside and San Bernardino Counties.
   Included under "Other districts."

- 13 Included under "Other districts."

  15 Exclusive of placer output, which is included under "Other districts."

  17 Exclusive of lode output, which is included under "Other districts."

  18 Includes following: Bishop Creek district in Inyo County; Daulton in Madera County; Bodie in Mono County; Rich Bar in Plumas County; Ivanpah in San Bernardino County; Figueroa Mountain in Santa Barbara County; Flat Creek, French Gulch (placer), and Redding (placer) in Shasta County; Brandw City and Downiewille (lode) in Sierra County; Humbug (placer) in Siskiyou County; Knights Ferry in Stanislaus County; Coffee Creek (lode) and Trinity Center (placer) in Trinity County; and Yuba Charty, Walth County. River in Yuba County.

19 Includes 71,000 pounds from precipitates.

#### AMADOR COUNTY

East Belt district.—The Belama Corporation worked the Belden mine in the Volcano section of the East Belt from January 1 until November 23, 1942. A lessee operated the Elk Horn mine from January 1 to May 1; 166 tons of gold ore containing 407 ounces of gold, 189 ounces of silver, and 2,621 pounds of copper were shipped to a smelter. Gold ore from the Fort Ann mine was amalgamated. The Garibaldi or Boardman property was operated by dragline and dry-land dredging; the dragline dredge recovered 775 ounces of gold and 102 ounces of silver from 172,200 cubic yards of gravel; and the dry-land dredge recovered 157 ounces of gold and 23 ounces of silver

from 35,500 cubic yards of gravel.

Mother Lode district.—The Argonaut Mining Co., Ltd., suspended operations at the Argonaut mine March 31, 1942; gold ore was treated by amalgamation and flotation, and the concentrates were evanided. The company also operated a 500-ton flotation plant at the Plymouth old tailings dump. While the Argonaut cyanide plant was in operation, the concentrates from the Plymouth old-tailings operation were cvanided but were shipped to a smelter later in the year. The Central Eureka Mining Co. operated the Old Eureka and Central Eureka mines from January 1 to October 1; ore was treated by amalgamation and flotation, and the sands and concentrates were cyanided. Kennedy Mining & Milling Co. operated the Kennedy mine until War Production Board Order L-208 ended operations which had been continuous since 1886. Lorentz & Swingle and the Long Bar Gold Dredging Co. operated dragline dredges on the Lorentz property on Cosumnes River; the company recovered 1,140 ounces of gold and 138 ounces of silver from 200,000 cubic yards of gravel. The Long Bar company also operated a dragline dredge on the Pension mine from September 13 to 28; 14,000 cubic yards of gravel yielded 87 ounces of gold and 12 ounces of silver. J. C. Pantle operated a dry-land dredge on the Rupley ranch on Willow Creek 5 miles west of Drytown from January 1 until October 15; 230,000 cubic yards of gravel yielded 1,290 ounces of gold and 183 ounces of silver; gravel was delivered to the dry-land dredge by a dragline excavator equipped with a 1½-cubic yard bucket.

#### BUTTE COUNTY

Butte Creek district.—The Lancha Plana Gold Dredging Co. operated a connected-bucket dredge on Butte Creek from January 1 to October 12, 1942; the dredge was of the Yuba type and had 65 4½-cubic foot buckets.

Oroville district.—F. C. Peterson operated a nonfloating washing plant on the Amo mine during 1942; 60,000 cubic yards of gravel yielded 379 ounces of gold and 12 ounces of silver. Yuba Consolidated Gold Fields, Butte Unit, operated four connected-bucket dredges on land adjoining Feather River from January 1 to October 15; all dredges were of the Yuba type and used electric power. The dredge-bucket equipment per boat was: 84 9-cubic foot, 89 9-cubic foot, 87 9-cubic foot, and 71 6-cubic foot buckets. The Golden Feather Dredging Co. operated a dragline dredge on the Feather River channel at Oroville throughout 1942. Because this operation cleared the channel of the river and stacked tailings along the levees, the company was permitted to continue operations after War Production Board

The second secon

Order L-208 became effective. The Placer Exploration Co. and Sunmar Dredging Co. operated dragline dredges on the Gianella property for short periods. The Placer Exploration Co. also carried on dragline dredging on the Innis property. In addition to the Gianella operation, the Sunmar Dredging Co. worked the Peter property. The Morris Ravine Mining Co. washed 850 cubic yards of gravel from which 658 ounces of gold and 65 ounces of silver were recovered;

the gravel was recovered by drift mining.

Yankee Hill district.—Hoefling Bros. operated the Surcease mine from January 1 to November 15, 1942; 27,480 tons of gold ore were treated in a 125-ton flotation-cyanidation mill; 713 ounces of gold and 89 ounces of silver were recovered by amalgamation of high-grade jig concentrates, and 6,630 ounces of gold and 15,907 ounces of silver were recovered by cyanidation of sands, slimes, and reground concentrates. Hoefling Bros. explored the nearby Big Bend prospect and, when War Production Board Order L-208 went into effect, intended to utilize the company organization and mill to develop the Big Bend zinc-copper ores.

## CALAVERAS COUNTY

Camanche district.—The Cat Camp Placers and Burson Mining Co. operated the Cat Camp mine during 1942; 71,818 cubic yards of gravel treated in nonfloating washing plants yielded 483 ounces of gold and 32 ounces of silver. E. A. Bacon recovered 286 ounces of gold and 14 ounces of silver from 10,000 cubic yards of gravel near Wallace; hydraulicking and a mechanical excavator were used.

Copperopolis district.—The Keystone Copper Co. unwatered and reopened the north shaft of the Keystone mine and started production in October 1942; 12,208 tons of copper ore were treated by flotation in the redesigned gold mill at the nearby Mountain King mine, and 1,619 tons of copper concentrates were shipped; the concentrates contained 15 ounces of gold, 602 ounces of silver, and 542,380 pounds

of copper.

Mother Lode district.—The Carson Hill Gold Mining Corporation treated 144,954 tons of gold ore at the Carson Hill mine between January 1 and May 31, 1942, and produced amalgamated bullion containing 4,173 ounces of gold and 404 ounces of silver; cyanidation bullion containing 5,242 ounces of gold and 2,400 ounces of silver; and 122 tons of gravity concentrates which, after partial extraction by amalgamation, contained 1,188 ounces of gold and 1,596 ounces of silver, when delivered to a smelter. On May 31 a fire destroyed the crushing, grinding, and flotation parts of the mill, and production was not resumed thereafter. According to the company printed annual report for the year ended September 30, 1942, the average recovery was \$2.18 per ton as compared with \$2.15 and \$2.19 for the years ended September 30, 1941 and 1940, respectively. According to the company engineer's report as of June 1, 1942, ore reserves in the Morgan Melones mine are estimated at 940,500 tons of a grade equal to that milled during the last 6 months of operation and 1,984,000 tons in the Calaveras mine of a grade estimated at \$5.76 per ton. W. Clark subleased the Val ranch and operated a stationary washing plant, to which gravel was delivered by power shovel and trucks, from May 7 to October 19; 6,245 cubic yards of gravel yielded 69 ounces of gold and 7 ounces of silver.

West Belt district.—E. A. Vogt carried on development work at the Collier mine during 1942 and shipped small lots of zinc and gold-silver ores. The property received a Reconstruction Finance Corporation Class B development loan October 12. In the same district the Mountain Copper Co., Ltd., and the Quail Hill Mining Co. conducted exploration campaigns at the Napoleon and Quail Hill mines, respectively. The ore bodies under development in the district contained zinc, copper, gold, and silver.

## ELDORADO COUNTY

Mother Lode district.—Alhambra-Shumway Mines, Inc., worked the Alhambra mine from March 1 to November 1, 1942; 2,305 tons of ore treated in the company 25-ton amalgamation mill yielded bullion containing 505 ounces of gold and 74 ounces of silver and 6 tons of flotation concentrates containing 34 ounces of gold and 3 ounces of silver. G. W. Gray recovered 80 ounces of gold and 5 ounces of silver from 1,000 pounds of quartz removed from a pocket at the Guttenberger property near Diamond Springs. The Barker Corporation operated a dragline dredge on the Explorers property from January 1 to August 29; 95,000 cubic yards of gravel yielded 754 ounces of gold and 94 ounces of silver. At the Good Luck mine 23,000 cubic yards of gravel yielded 164 ounces of gold and 22 ounces of silver; 14,000 cubic yards of gravel washed at the Max & Junction mine yielded 110 ounces of gold and 15 ounces of silver; 77,500 cubic yards of gravel washed at the Setter property yielded 548 ounces of gold and 70 ounces of silver.

West Belt district.—C. D. Jones operated the Boulder mine in the Rescue section of the West Belt from March to October 15, 1942; 280 tons of gold ore treated by amalgamation yielded 122 ounces of gold and 13 ounces of silver. The Big Canyon Dredge operated a dragline dredge from January 1 to July 31; 1,269 ounces of gold and 137 ounces of silver were recovered from 250,000 cubic yards of gravel; the dragline excavator was equipped with a 3-cubic yard bucket.

#### FRESNO COUNTY

Friant district.—Griffith Co. and Bent Co., which supplied gravel for the Friant Dam in 1942, recovered 205 ounces of gold and 29 ounces of silver in preparing 121,700 cubic yards of sand and gravel. The Twin Bar Mining Corporation operated a dredge on the Grant Pacific Rock and V. Roulard properties from March to October 23. Hopkins & Becker operated a suction dredge on San Joaquin River near Friant. The Grant-Service Rock Co. recovered 114 ounces of gold and 16 ounces of silver in preparing 339,955 tons of sand and gravel for concrete aggregate.

#### IMPERIAL COUNTY

Mesquite Diggings (Glamis) district.—Van Derpoel & Murphy operated the Mary Lode mine from January 1 to July 15, 1942, when operations were suspended because of war conditions; 186 tons of ore treated in the company 25-ton amalgamation-cyanidation mill yielded 109 ounces of gold and 136 ounces of silver.

#### INYO COUNTY

Bishop Creek district.—The United States Vanadium Corporation produced by flotation a copper concentrate containing a substantial quantity of silver per ton as a byproduct of ore treated primarily for tungsten. This company was the leading copper producer in the State in 1942.

Cerro Gordo district.—Desert Miners shipped zinc-lead ore from the Leavy mine in the Swansea section of the Cerro Gordo district

during 1942.

Coso (Darwin) district.—The Imperial Metals, Inc., operated the Defiance, Independence, Essex, Thompson, Lucky Jim, Lane, Promontory, and Columbia mines as a unit during 1942; a newly constructed 150-ton gravity-concentration and flotation mill began operations June 20 and continued until November 23, when unsatisfactory metallurgical results and inability to hire experienced workmen forced suspension of milling. In addition, the company made shipments of crude ore, which were continued after mill operations were suspended. The milling of 11,415 tons of silver ore produced 790 tons of lead concentrates, containing 57 ounces of gold, 22,989 ounces of silver, and 612,000 pounds of lead; shipments of 2,823 tons of lead ore contained 117 ounces of gold, 26,887 ounces of silver, and 850,000 pounds of lead.

Modoc district.—The Combined Metals Reduction Co. operated the Colorado group throughout 1942; zinc sulfide ore was shipped to the

company concentrating mill at Bauer, Utah.

Resting Springs district.—Shoshone Mines, Inc., shipped ore from the Columbia No. 2 mine throughout 1942 and was by far the largest producer of lead and third-largest producer of silver in the State; 24,999 tons of ore contained 4,770 ounces of gold, 210,503 ounces of silver, 14,710 pounds of copper, 8,425,760 pounds of lead, and 2,789,540 pounds of zinc.

Sherman district.—Burton Bros. (partnership) operated the Ruth mine and treated 19,961 tons of ore by crushing and cyanide leaching in 1942; 3,674 ounces of gold and 102 ounces of silver were recovered before operations were suspended November 1 because of War Pro-

duction Board Order L-208.

State Range district.—L. E. Damon shipped lead ore from the Gold Bottom mine during 1942. C. O. Mittendorf, lessee, operated the Ophir mine through sublessees from January to September and shipped to a smelter 501 tons of lead ore containing 4 ounces of gold, 2,215 ounces of silver, and 246,440 pounds of lead.

South Park district.—The Southwest Lead & Zinc Co. operated the Honolulu mine from April 1 to December 31, 1942, and shipped zinc-

lead and lead ores to a smelter.

#### KERN COUNTY

Cove district.—Kern Mines, Inc., operated the Big Blue mine from January 1 to July 1, 1942; 16,467 tons of ore yielded amalgamation bullion, containing 1,054 ounces of gold and 460 ounces of silver, and 346 tons of flotation concentrates, containing 1,271 ounces of gold, 4,180 ounces of silver, and 11,216 pounds of lead.

Mojave district.—The Cactus Mines Co. operated the Cactus Queen mine in the Middle Buttes section of the Mojave district from January

1 to November 20, 1942, and treated gold-silver ore in the company 125-ton cvanidation-flotation mill; the resulting concentrates were shipped to a smelter. This property was California's leading silver producer for the fifth successive year. Lessees shipped 950 tons of gold ore from the Elephant-Eagle mine to nearby custom cyanide mills; 612 ounces of gold and 71 ounces of silver were recovered. Lessees worked the Middle Butte mine; 125 tons of ore treated by amalgamation, 165 tons of ore shipped to a custom cyanide mill, and 175 tons of old tailings cyanided yielded amalgamation bullion containing 15 ounces of gold and 4 ounces of silver and cyanide bullion containing 68 ounces of gold. Burton Bros., Inc., operated the Tropico mine from January 1 to November 1; 18,044 tons of gold ore treated in the company 100-ton cyanide mill yielded 5,353 ounces of gold and 11,850 ounces of silver. In addition, the company treated over 4,783 tons of custom material from 65 shippers during 1942 compared with over 8,800 tons of custom material from 215 shippers in 1941. When the Burton Bros., Inc., mill ceased to accept custom ores, a number of mines within a radius of 100 or more miles of Rosamond were left without an economic market for their ores, as all other custom mills in the region had alread discontinued milling.

Randsburg district.—E. B. Atkinson shipped 357 tons of ore from the Earl & Matilda mine to a custom cyanide mill in 1942; 68 ounces of gold and 11 ounces of silver were recovered. S. D. Fraser and lessees operated the K. C. N. mine from January 1 to August 15; 234 tons of ore shipped to custom cyanide mills yielded 175 ounces of gold and 8 ounces of silver. King Solomon Mines Lease worked the King Solomon mine from January 1 to April 30; 285 tons of ore treated by amalgamation yielded 76 ounces of gold and 21 ounces of silver, and 150 tons of old tailings treated by cyanidation yielded 7 ounces of gold and 3 ounces of silver. The Anglo American Mining Corporation, Ltd. largest operator in the Randsburg district—treated 300,755 tons of old tailings and recovered 6,075 ounces of gold and 2,691 ounces of silver from January 1 to October 23, when operation was suspended by War Production Board Order L-208. The Rand Gold Dredging Associates installed a connected-bucket-type dredge with 82 3-cubic foot buckets to work gravels at a property 11/4 miles northwest of Randsburg; the dredge was moved from Shasta County, where it had formerly been operated by the Roaring River Dredging Co. dredge was reconstructed and jigs were added in order to recover scheelite as well as gold; operations started November 1. The Monarch Rand Mining Co. operated a dry-land dredge for the recovery of The second secon

#### LOS ANGELES COUNTY

scheelite and gold intermittently over a 6-month period.

Cedar district.—The Governor Mine Co. turned over operation of the Governor and Red Rover mines to G. Moore February 16, 1942, and all work was suspended October 15; during the year 870 tons of ore were treated by amalgamation and flotation in the company 135-ton mill; 78 ounces of gold and 15 ounces of silver were recovered in bullion, and 14 tons of concentrates shipped to a smelter contained 39 ounces of gold and 24 ounces of silver.

#### MADERA COUNTY

Daulton district.—The West Lode Reduction Co. pumped copperbearing water from the Daulton mine, which was percolated through old dumps at the property and the copper precipitated on scrap iron during 1942; the cement copper was shipped to a manufacturer of copper sulfate. Copper ore from the Jessie Bell mine was shipped to a copper smelter.

Potter Ridge district.—G. E. Noble & Sons operated a suction dredge on the J. T. Pierce ranch from January 1 to December 12, 1942; 7,790 cubic yards of gravel yielded 118 ounces of gold and 35 ounces of Suction-dredge operations on the Polk ranch recovered 148 ounces of gold and 32 ounces of silver from 9,000 cubic yards of gravel.

#### MARIPOSA COUNTY

East Belt district.—R. J. Wilson operated the Feliciana mine throughout 1942; 3,211 tons of gold ore treated by amalgamation and concentration in a 25-ton mill yielded amalgamation bullion containing 1,535 ounces of gold and 236 ounces of silver and 49 tons of flotation concentrates containing 403 ounces of gold and 78 ounces of silver; the concentrates were shipped to a smelter. Schroeder, Odgers & Schroeder worked the Schroeder mine in the Colorado section of the East Belt throughout the year; 39 tons of gold ore treated in a 20-ton Huntington mill yielded 716 ounces of gold and 88 ounces of silver. The Whitlock mine was active.

Hunter Valley district.—E. L. Buerki operated the Ruth Pierce mine throughout 1942 and treated 1,620 tons of old tailings, which yielded 94 ounces of gold and 59 ounces of silver; the old tailings were given a 96-hour leach in a 15-ton plant. Thurman & Wright operated a dragline dredge on Burns Creek from January 1 to August 20; the dragline-excavator equipment included 41/2- and 6-cubic foot The Trebor Corporation, which suspended operations at the Gaskill property on Corbett Creek 8 miles west of Mariposa December 30, 1941, shipped 68 ounces of gold and 12 ounces of silver from the final clean-up of the operation; the dragline excavator was equipped with a 2-cubic yard bucket. The Barker Corporation operated a dragline dredge on the Kehoe, J. Lord, and Trabucco properties between January 1 and July 1, 1942; 22,000 cubic yards of gravel washed at the Kehoe property yielded 112 ounces of gold and 32 ounces of silver; 109,000 cubic yards of gravel at the J. Lord property yielded 833 ounces of gold and 229 ounces of silver; and 163,500 cubic yards of gravel at the Trabucco property yielded 1,016 ounces of gold and 280 ounces of silver.

Mother Lode district.—The Mount Gaines Mining Co. worked the Mount Gaines mine throughout 1942; 11,263 tons of gold ore yielded amalgamation bullion containing 3,664 ounces of gold and 1,134 ounces of silver and 337 tons of flotation concentrates containing 3,281 ounces of gold, 1,117 ounces of silver, 2,027 pounds of copper, and 583 pounds of lead; the concentrates were shipped to a smelter. The Pacific Mining Co. worked the Pine Tree and Josephine mines; 50,697 tons of ore yielded amalgamation bullion containing 233 ounces of gold and 52 ounces of silver and 959 tons of flotation concentrates containing 6,056 ounces of gold, 1,450 ounces of silver, and 1,213 pounds of copper. The Trebor Corporation operated the C. C. Pierce property on Corbett Creek for 3½ months in 1942; 100,000 cubic yards of gravel yielded 289 ounces of gold and 57 ounces of silver; the equipment was the same as that used on another section of Corbett Creek in the Hunter Valley district.

## MERCED COUNTY

Snelling district.—The Merced Dredging Co. operated a connected-bucket dredge with 60 9½-cubic foot buckets on Merced River ¾ of a mile southeast of Snelling from January 1 to October 13, 1942. The San Joaquin Mining Co. operated a connected-bucket dredge in the Merced River Valley 3 miles southwest of Snelling from January 1 to October 14; the dredge was equipped with 64 9½-cubic foot buckets. The Snelling Gold Dredging Co. began 1942 with two dredges operating on Merced River between Snelling and Merced Falls; dredge No. 1 with 66 7-cubic foot buckets was closed down March 31, and dredge No. 2 with 72 7-cubic foot buckets suspended operations October 15 because of War Production Board Order L-208.

## MONO COUNTY

Blind Springs district.—Conversion of the Mineral Reduction Co. cyanide-flotation custom mill from the treatment of gold and silver ores to tungsten ores early in 1942 left many of the mines in the Blind Springs district and surrounding territory without a market for their ores.

## NEVADA COUNTY

Grass Valley-Nevada City district.—The Empire Star Mines Co., Ltd., operated the Empire, North Star, and Pennsylvania mines at Grass Valley in Nevada County and the Pennsylvania and Dannebrog at Browns Valley in Yuba County during 1942; in addition, work on a tailings-disposal adit from the South Fork of Yuba River near Omega to the Zeibright mine was carried on during the early months of the year. Ore mined in the Empire-North Star-Pennsylvania group was treated in the company amalgamation-cyanidation-flotation mill; all productive operations were suspended by War Production Board Order L-208, but a crew of over 100 men was retained for maintenance purposes. The Idaho Maryland Mines Corporation operated the Idaho Maryland-Brunswick group from January 1 to October 15; according to the company printed annual report for the year ended December 31, 1942, 144,639 tons of ore yielded 53,342 ounces of gold and 14,700 ounces of silver. Of the year's total tonnage, 17.4 percent was derived from development or exploration and the remainder from stoping. The Brunswick mill was closed April 30, and one of the two units of the Idaho mill was operated part time. During the year the new Brunswick steel head frame, crusher plant, hoist, and compressor buildings were completed; this equipment was designed to handle 2,000 tons a day from depths of 5,000 feet. creasing labor shortages curtailed production. When War Production Board Order L-208 went into effect, 245 men were employed compared with a daily average of 1,000 men in 1940; after the order the crew was reduced to 125 men for mine and plant maintenance. The Lava Cap Gold Mining Corporation operated the Lava Cap

THE REPORT OF THE PARTY OF THE

mine throughout 1942; 137,194 tons of ore were treated by amalgamation, flotation, and cyanidation in the company 400-ton flotation plant, 25-ton concentrate- and middling-cyanide plant, and 350-ton tailings-cyanide plant. Cyanidation of sands, slimes, and middlings yielded 2,245 ounces of gold and 15,558 ounces of silver; amalgamation of high-grade ore yielded 113 ounces of gold and 29 ounces of silver; 4,912 tons of flotation concentrates shipped to a smelter contained 30,804 ounces of gold, 233,130 ounces of silver, 21,048 pounds of copper, and 13,600 pounds of lead.

North Bloomfield district.—A. B. Innis operated a dragline dredge at the Malakoff mine during 1942; 146,000 cubic yards of gravel yielded 694 ounces of gold and 64 ounces of silver.

Washington district.—The Omega Co. and lessees operated the Omega mine from January 17 to July 7, 1942; 818,175 cubic yards of gravel yielded 1,749 ounces of gold and 54 ounces of silver.

## ORANGE COUNTY

Santa Rosa district.—The Blue Light Silver Mines Co. worked the Silverado or Blue Light mine in Silverado Canyon from January to June 1942; 100 tons of silver ore treated by flotation yielded 5 tons of lead concentrates containing 2 ounces of gold, 470 ounces of silver, 2.538 pounds of lead, and 1,517 pounds of zinc, and 7 tons of zinc concentrates containing 80 ounces of silver and 7,596 pounds of zinc; the concentrates were shipped to smelters. In addition, 18 tons of silver ore, containing 3 ounces of gold and 2,195 ounces of silver, were shipped to a smelter. The Ortega Mining Co. shipped argentiferous lead ore from the district.

#### PLACER COUNTY

Auburn district.—G. M. Trent shipped to a smelter 43 tons of goldsilver ore containing 9 ounces of gold, 150 ounces of silver, 776 pounds of copper, and 670 pounds of lead while developing the Valley View

mine during 1942.

Ophir district.—The Alabama California Gold Mines Co. operated the Alabama mine from January to August 1942; ore was treated by amalgamation and flotation, and the resulting concentrates were shipped to a smelter; amalgamation bullion contained 8,391 ounces of gold and 2,575 ounces of silver, and 496 tons of flotation concentrates contained 2,149 ounces of gold, 25,919 ounces of silver, 5,442 pounds of copper, and 25,927 pounds of lead. Exploration and development continued at the Ophir mine from January 1 until September 1; test runs were made by amalgamation, cyanidation, concentration, and direct smelting on small tonnages of ore; in all, 184 tons of ore yielded 86 ounces of gold, 196 ounces of silver, and 3,288 pounds of copper. The Oro Fino Consolidated Mines operated the Oro Fino mine from January 1 to October 8; 9,058 tons of ore treated in the company 200-ton amalgamation-flotation mill yielded amalgamation bullion containing 3,535 ounces of gold and 1,423 ounces of silver; and 125 tons of concentrates, which were cyanided in the custom cyanide plant, yielded 522 ounces of gold and 224 ounces of silver.

#### PLUMAS COUNTY

Greenville (Crescent Mills) district.—Cherokee Mine operated the Cherokee property from January 1 to July 15, 1942, when the property was abandoned; 13,392 tons of ore treated by cyanidation yielded 2,331 ounces of gold and 59 ounces of silver.

## SACRAMENTO COUNTY

Cosumnes River district.—The Cosumnes Gold Dredging Co. operated a connected-bucket dredge 7 miles southwest of Sloughhouse from January 1 to October 20, 1942; the dredge used electric power and was equipped with 63 12-cubic foot buckets. Hoosier Gulch Placers operated two dragline dredges in the Cosumnes River district during 1942. The Humphreys Gold Corporation operated a dragline dredge on Cosumnes River from January 1 to April 6; the floating washing plant was served by four dragline excavators, each equipped with a 2½-cubic yard bucket, which stripped overburden as well as

delivered auriferous gravel to the plant.

Folsom district.—The Capital Dredging Co. operated two electric connected-bucket dredges on its property 5 miles south of Folsom from January 1 to October 15, 1942; one dredge had 88 and the other 100 18-cubic foot buckets. The General Dredging Co. operated three dragline dredges, one near Folsom, the second near Natoma, and the third near Fair Oaks. Cutter & Mueller and the Pacific Coast Aggregates, Inc., recovered gold as a byproduct in the operation of a commercial sand and gravel plant at Fair Oaks; Cutter & Mueller recovered 183 ounces of gold and 15 ounces of silver from 40,320 cubic yards of gravel, and Pacific Coast Aggregates, Inc., recovered 111 ounces of gold and 11 ounces of silver. The Lancha Plana Gold operated a dragline dredge at Sailor's Co. on American River from January 1 to November 11, 1942. The Natomas Co. operated a fleet of seven electric connected-bucket dredges at and near Natoma from January 1 to October 15. number and size of buckets per dredge were: No. 1, 62 16-cubic foot; No. 4, 67 15-cubic foot; No. 5, 105 12-cubic foot; No. 6, 106 11-cubic foot; No. 7, 98 9-cubic foot; No. 8, 105 12-cubic foot; and No. 10, 83 15-cubic foot.

#### SAN BERNARDINO COUNTY

Buckeye district.—The Bagdad-Chase, Ltd., operated the Bagdad-Chase mine from January 1 to December 31, 1942; gold ore, containing a substantial quantity of silver and copper, was shipped to a smelter.

Calico district.—M. La Jeunesse operated a cyanide-leaching plant on wind-blown tailings from the Calico tailings dump from January 1 to May 15, 1942; 370 tons of old tailings yielded 1,084 ounces of silver. L. Coke shipped silver ore from the Zenda mine.

Dale district.—L. A. Wilson operated the Glad-Stone, Gold-Stone, and Desert-Gold mining claims from January 1 to June 2, 1942; 243 tons of ore, shipped to custom cyanide mills, yielded 371 ounces of

gold and 125 ounces of silver.

Ivanpah district.—W. F. Huston operated the Carbonate King mine from January 1 to December 31, 1942; 749 tons of oxidized zinc

The Control of the Co

THE REPORT OF THE PARTY OF THE

ore, containing 1 ounce of gold, 543 ounces of silver, 16,745 pounds of lead, and 567,163 pounds of zinc, were shipped to smelters.

New York Mountains district.—The California Sulphur Co. carried on development work at the Sagamore mine (Alpha claims) from June until December 31, 1942; 114 tons of lead ore, containing 1 ounce of gold, 682 ounces of silver, 3,481 pounds of copper, and 14,597 pounds of lead, were shipped to smelters.

## SAN JOAQUIN COUNTY

Camanche district.—The Gold Hill Dredging Co. operated two electric connected-bucket dredges on the California Lands, Inc., Central Bank of Calaveras, Thorne, and Putnam properties during 1942; one dredge had 66 7%-cubic foot buckets and the other 87 8%-cubic foot buckets. Both dredges ceased operations October 14, but one resumed work December 20 and continued until December 31. The Lobicasa Co. operated a dragline dredge, using a dragline excavator with a 1%-cubic yard bucket, on the Foster ranch from January 1 to May 14, when the property was worked out and abandoned. The Gold Valley Dredging Co. operated a dry-land washing plant, to which gravel was delivered by a gasoline dragline excavator with a %-cubic yard bucket, at the Murdoch ranch from February 25 to May 24; 9,316 cubic yards of gravel yielded 83 ounces of gold and 6 ounces of silver.

Jenny Lind (Bellota, Linden) district.—Smith-Notterman Co. operated a dragline dredge with a dragline excavator having a 1%-cubic yard bucket on the Elmer Cady ranch from January to March 26, 1942; 93,105 cubic yards of gravel yielded 344 ounces of gold and

14 ounces of silver.

#### SHASTA COUNTY

Flat Creek district.—The Mountain Copper Co., Ltd., largest mineral producer in Shasta County, worked the Iron Mountain mine throughout 1942; oxidized ore was treated in the company 700-ton cyanide plant until plant operation was suspended in February. Mining of copper-bearing sulfide ores was begun in May, and shipments to a smelter continued during the rest of the year; in addition, the company was engaged in opening a large zinc-copper ore body and constructing a flotation mill for its treatment. A small quantity of gold, silver, and copper was recovered from smelting cinder derived from burning pyrites in a sulfuric acid plant; the pyrites was produced by the Mountain Copper Co., Ltd., at the Hornet mine.

Igo district.—B. H. K. Mines operated a dragline dredge, using a dragline excavator with a 1%-cubic yard bucket, on the R. C. Connely and R. Litsch properties on Clear Creek from January 1 to May 15, 1942; 120,000 cubic yards of gravel yielded 760 ounces of gold and 104 ounces of silver. The Lincoln Gold Dredging Co. operated a dragline dredge with a dragline excavator having a 2%-cubic yard bucket on the Brady property; 37,234 cubic yards of gravel yielded 162 ounces of gold and 26 ounces of silver. The Clear Creek Dredging Co. operated a dragline dredge on Clear Creek, The Crow Creek Dredging Co. operated a dragline dredge, using a dragline excavator with a 1½-cubic yard bucket, on Cottonwood Creek from January 1 to April 13, 1942; 100,000 cubic yards of gravel

yielded 580 ounces of gold and 20 ounces of silver. The Dobbin Gulch Dredging Co. operated a dragline dredge with a dragline excavator having a 1½-cubic yard bucket on Roaring River from March 3 to June 2; 70,500 cubic yards of gravel yielded 169 ounces of gold and 11 ounces of silver. The Thurman Gold Dredging Co. operated a Yuba electric connected-bucket dredge, equipped with 72 9-cubic foot buckets, on Clear Creek from January 1 to October 14, 1942.

SIERRA COUNTY

Alleghany district.—The Original Sixteen to One Mine, Inc., operated its Original Sixteen to One mine throughout 1942; in addition to underground work, a lessee treated old tailings at the property. J. Sweeney operated the Snow Drift mine from March to September; 111 tons of ore yielded 145 ounces of gold and 23 ounces of silver.

Downieville district.—Wm. Richter & Sons operated a dragline dredge on Pacific Gas & Electric Co. property from January 1 to April 30; 58,000 cubic yards of gravel yielded 243 ounces of gold and

29 ounces of silver.

Pike (Slate Range) district.—H. L. Sorensen operated the Alaska mine from January 1 to October 10 and treated 388 tons of ore by amalgamation, which yielded 547 ounces of gold and 185 ounces of silver; during the year development was shifted from the Alaska to the Grizzly vein. W. C. Ennis operated the Bowman mine from January 1 to December 31; 3,140 tons of ore yielded 480 ounces of gold and 85 ounces of silver.

Poker Flat (Port Wine, Table Rock) district.—A. J. Just carried on hydraulicking at the Pioneer Project mine at Grass Flat for 10 days during 1942; 17,000 cubic yards of gravel yielded 71 ounces of gold and 4 ounces of silver. C. S. Poor worked the Tennessee Manxman drift mine throughout the year; 1,200 cubic yards of gravel yielded

142 ounces of gold and 16 ounces of silver.

#### SISKIYOU COUNTY

Callahan district.—The Okoro Mines, Inc., operated a dragline dredge on the Hayden property from January 1 to 31, 1942; 60,000 cubic yards of gravel yielded 103 ounces of gold and 10 ounces of silver.

Greenhorn district.—The Lincoln Gold Dredging Co. operated a dragline dredge on the City of Yreka, General Dredge, Marlow, Nunes, and Rose properties from January 1 to July 21, 1942; the dragline excavator was equipped with a 2½-cubic yard bucket. The following data on yardages washed and precious metal recovered were reported: City of Yreka property, 43,029 cubic yards of gravel yielded 304 ounces of gold and 44 ounces of silver; General Dredge property, 272,423 cubic yards of gravel, 1,844 ounces of gold and 263 ounces of silver; and Nunes property, 31,128 cubic yards of gravel, 259 ounces of gold and 37 ounces of silver.

Klamath River district.—The Gray Eagle Copper Co. reopened the Dakin copper mine near Happy Camp and constructed a 550-ton flotation mill during 1942; no shipments of ore or concentrates were made. The William von der Hellen Mining Co. operated a dragline dredge, using a dragline excavator with a 3-cubic yard bucket, on

さいまでいるという

McConnell Bar from January 1 to September 27; 596,800 cubic yards

of gravel yielded 3,594 ounces of gold and 554 ounces of silver.

Liberty district.—N. Marvin worked the Hansen mine during 1942. A. Markon operated the Surprise mine on Eddys Gulch from March 2 to November 28, 1942; 148 tons of ore treated by amalgamation yielded 78 ounces of gold and 15 ounces of silver. F. R. Jackson worked the J. F. Judge hydraulic mine from January 1 to July 1; 22,000 cubic yards of gravel yielded 238 ounces of gold and 33 ounces of silver.

#### STANISLAUS COUNTY

Knights Ferry district.—Placer Properties Co. operated a dragline dredge on Stanislaus River from January 1 to October 15 and from November 15 to December 31, 1942; two dragline excavators, one with a 6-cubic yard bucket and the other with a 2 ½-cubic yard bucket, were used.

#### TRINITY COUNTY

Crow Creek district.—C. L. Kalbaugh operated a suction dredge and tractor on the Thursday No. 1 mine on Crow Creek from May 1 to September 15, 1942; 103 ounces of gold were recovered from 1,000 cubic yards of gravel.

Junction City district.—Junction City Mining Co. operated an electric connected-bucket dredge with 72 9-cubic foot buckets from January 1 to October 28, 1942; 2,077,000 cubic yards of gravel yielded

7,878 ounces of gold and 735 ounces of silver.

Lewiston district.—The Lincoln Gold Dredging Co. operated a dragline dredge, using a dragline excavator with a 21/2-cubic yard bucket, on the Costa property on Rush Creek from January 1 to September 12, 1942; 271,744 cubic yards of gravel yielded 1,406 ounces of gold and 95 ounces of silver. Lewiston Placers hydraulicked at the Lewiston Placers mine from January 1 to June 30; 75,000 cubic yards of gravel

yielded 188 ounces of gold and 24 ounces of silver.

Weaverville district.—The La Grange Placer Mines, Ltd., hydraulicked 250,000 cubic yards of gravel, which yielded 548 ounces of gold and 52 ounces of silver, at the La Grange Placers mine from January 1 to July 1, 1942. The Dobbin Gulch Dredging Co. operated a dragline dredge, which had a dragline excavator with a 11/4-cubic yard bucket, at the Sunshine and M. A. Brady properties from January 3 to October 19, 1942; at the Sunshine mine 107,300 cubic yards of gravel yielded 348 ounces of gold and 33 ounces of silver.

#### TULARE COUNTY

White River district.—The Thanksgiving Mining Co. operated the Thanksgiving mine from January 1 to September 1, 1942; 315 tons of ore treated by amalgamation and flotation yielded bullion containing 61 ounces of gold and 22 ounces of silver and concentrates (shipped to a smelter) containing 69 ounces of gold and 28 ounces of silver.

## TUOLUMNE COUNTY

Mother Lode district.-Miller & Clemson operated the Eagle-Shawmut mine from January 1 to December 31, 1942; 143,866 tons of ore treated in a 500-ton flotation mill yielded bullion containing 607

ounces of gold and 164 ounces of silver and 3, 865 tons of concentrates containing 10,687 ounces of gold, 3,270 ounces of silver, and 7,483 pounds of copper; the concentrates were shipped to a smelter. E. A. Kent operated a dragline dredge with a dragline excavator having a 2½-cubic yard bucket on the Lyons and Rosasco ranches from January 2 to February 19, 1942; 224 ounces of gold and 15 ounces of silver were recovered from 53,000 cubic yards of gravel at the Lyons ranch, and 308 ounces of gold and 21 ounces of silver were recovered from 52,500 cubic yards of gravel at the Rosasco ranch.

#### YUBA COUNTY

Smartville district.—The Williams Bar Dredging Co. operated a connected-bucket dredge equipped with 84 6-cubic foot buckets in the bed of Yuba River near Smartville throughout 1942; 2,872,327 cubic yards of gravel yielded 6,354 ounces of gold and 447 ounces of silver.

# GOLD, SILVER, COPPER, LEAD, AND ZINC IN THE CENTRAL **STATES**

(MINE REPORT)

By A. J. MARTIN

## SUMMARY OUTLINE

	Page !		Page
Commount	295	Review by States—Continued.	10.00
Summary	295	Illinois	299
Calculation of value of metal production		Kansas	300
Mine production by States and regions	297	Kentucky	302
Mine production of lead and zinc by regions.	297		303
Quantity and tenor of ores	298	Michigan	
Mining and metallurgic industry	298	Missouri	305
	299	Oklahoma	312
Review by States		Wisconsin	315
Arkansas	299	11 1000110111	310

## SUMMARY

The mine production of recoverable silver, copper, and zinc in the Central States decreased in 1942 compared with 1941, but that of lead increased. No output of gold was reported in either year, and the silver produced was derived from base-metal ores. increase in lead output resulted from capacity operation of the large lead mines in Southeastern Missouri. The decreases in copper and zinc, despite intensified activity in mining, can be attributed to The developed high- and medium-grade ore reserves several factors. were drawn upon heavily in 1940 and 1941 to help meet quickly the expanding requirements of metal for armaments. Operating margins under the controlled and ceiling metal prices prevailing after September 23, 1940, generally were insufficient to meet the increases in operating costs and also provide for extensive new development The full potential effect of the premium-price plan and prospecting. and other measures taken by Federal agencies to get production from marginal and submarginal ores was not reflected in output during the year, owing to the length of time required to reopen and reequip old properties and bring newly found ore bodies to the productive stage. Labor shortages and delay in getting delivery of some materials, such as steel products and electrical equipment, reduced output at some mines.

All tonnage figures are short tons and "dry weight"; that is, they

do not include moisture.

The value of metal production herein reported has been calculated at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zinc 4
1938	 Per fine ounce \$35.00 35.00 35.00 35.00	Per fine ounce \$ \$0.646+ 6.678+ 7.711+ 7.711+ 7.711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057 .067	Per pound \$0.048 .052 .063 .075 .093

1 Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.

2 Treasury buying price for newly mined silver.

3 1838-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.

4 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.

5 30.64646464.

5 30.67878787.

7 \$0.71111111.

295

THE PARTY OF THE P

Mine production of gold, silver, copper, lead, and zinc in the Central States, 1938-42, in terms of recovered metals

		Mines	Ore	and		Gold			Silver
Year		producing	old tailings (short tons)		Fin ounc		lue	Fine ounce:	
1938		229 251 416 447 502	22, 97 25, 53 28, 95	7, 105 2, 151 2, 085 9, 189 6, 994		14	\$140 175	386, 21 315, 95 353, 73 448, 82 130, 88	3 214, 465 7 251, 546 4 319, 164
	Cop	per	I	ead			Zinc		
Year	Pounds	Value	Short tons	Va	lue	Short tons	,	Value	Total value
1938 1939 1940 1941 1942	93, 486, 000 87, 970, 000 91, 766, 000 95, 680, 000 93, 958, 000	\$9, 161, 628 9, 148, 880 10, 369, 558 11, 290, 240 11, 368, 918	158, 873 198, 481 207, 587 209, 362 235, 229	\$14, 610 18, 657 20, 750 23, 867 31, 520	7, 214 8, 700 7, 268	198, 721 231, 716 244, 976 276, 006 258, 181	24, 30, 41,	077, 216 098, 464 866, 976 400, 900 021, 666	\$43, 104, 831 52, 119, 163 62, 246, 955 76, 877, 572 91, 004, 343

<sup>1</sup> From placer prospecting.

Silver.—Silver output in the Central States in 1942 comprised 69,106 ounces derived from refining lead bullion, slags, and skimmings recovered from Southeastern Missouri lead ores; 61,674 ounces from Michigan copper ore; and 104 ounces from galena concentrates recovered in milling Illinois zinc-lead ore and fluorspar. Output of silver-bearing lead concentrates from Southeastern Missouri increased in 1942 and their average silver content per ton (about 1.5 ounces) was approximately the same as in other years, but the bulk of the silver was not recovered in the smelter production of chemical (undesilverized) lead and was therefore not included in the production figures for recoverable silver.

Copper.—Copper mines in Michigan yielded 97 percent of the Central States total output of recoverable copper in both 1941 and 1942. The State output was 91,358,000 pounds of refined copper in 1942, and the average recovery per ton of combined rock and sands treated was 20.9 pounds compared with 92,880,000 and 21.7 pounds, respectively, in 1941. The huge war demand for copper and the payment of the Government premium for copper produced in excess of quotas stimulated exploration and development work at Michigan mines. No copper ore was produced in any of the other Central States in 1942. The Missouri production of copper (2,600,000 pounds) was derived from treatment of residues from the smelting of lead concentrates from Southeastern Missouri.

Lead.—Of the 235,229 tons of recoverable lead produced by mines in the Central States in 1942, 197,291 tons (84 percent) came from Southeastern Missouri. The large mines of the St. Joseph Lead Co. in this region contained appreciable reserves of developed ore, which were drawn upon to prevent a shortage of lead for war purposes. The Tri-State region (Kansas, Oklahoma, and Southwestern Missouri) yielded 34,341 tons of lead during the year and Arkansas, Central Missouri, Illinois, Kentucky, and Wisconsin together 3,597 tons. The output from Southeastern Missouri increased 32,949 tons over

1941, but the combined output of the other regions decreased 7,082 tons.

Zinc.—Although activity in zinc and zinc-lead mining in the Central States continued to expand during 1942 and many old mines were reopened, the output of recoverable zinc dropped 6 percent below that in 1941; the largest decrease in quantity was 20,901 tons (8 percent) in the Tri-State region, which yielded 92 percent of the total in 1942, 94 percent in 1941, 95 percent in 1940, and 97 percent in 1939. In 1942 Oklahoma contributed 62 percent and Kansas 23 percent of the Tri-State output compared with 64 and 28 percent, respectively, in 1941. A general review of mining and milling in the Tri-State region is given in the pages of this chapter devoted to Southwestern Missouri. Production of zinc in Illinois increased from 9,198 tons in 1941 to 9,389 tons in 1942 and that in Wisconsin from 6,238 to 9,426 tons; in Southeastern and Central Missouri the combined output decreased from 1,100 to 842 tons; in Kentucky the output decreased from 427 to 407 tons and in Arkansas from 206 to 181 tons.

## MINE PRODUCTION BY STATES AND REGIONS

Mine production of silver, copper, lead, and zinc in the Central States in 1942, by States, in terms of recovered metals

	14-4-		Mines	oro-		nd old	Silv	er
	State		ducin			s (short  -	Fine ounces	Value
Arkansas Illinois Kansas				33 19 81		4, 595 1 86, 796 872, 052	104	\$74
Kentucky Michigan Missouri Oklahoma Wisconsin				7 9 118 141 94	9,	1 2, 056 362, 640 298, 758 798, 423 301, 674	61, 674 69, 106	43, 857 49, 142
Total, 1941				502 447		726, 994 959, 189	130, 884 448, 824	93, 073 319, 164
	Cop	pper	I	æad			Zine	
State	Pounds	Value	Short tons	v	alue	Short tons	Value	Total value
Arkansas Illinois Kansas Kentucky Michigan		\$11,054,318	2, 344 9, 419 335		\$268 314, 096 262, 146 44, 890	181 9, 389 55, 874 407	\$33, 666 1, 746, 354 10, 392, 564 75, 702	\$33, 934 2, 060, 524 11, 654, 710 120, 592 11, 098, 175
Missouri Oklahoma Wisconsin	2, 600, 000	314,600	199, 548 22, 806 775	3,0	739, 432 056, 004 103, 850	36, 394 146, 510 9, 426	6, 769, 284 27, 250, 860 1, 753, 236	33, 872, 458 30, 306, 864 1, 857, 086
Total, 1941	93, 958, 000 95, 680, 000	11, 368, 918 11, 290, 240	235, 229 209, 362		520, 686 367, 268	258, 181 276, 006	48, 021, 666 41, 400, 900	91, 004, 343 76, 877, 572

<sup>&</sup>lt;sup>1</sup> Excludes lead-bearing material mined with fluorspar and from which some lead was recovered as a byproduct of the mining and milling of the fluorspar.

Of the seven lead- and zinc-producing regions in the Central States, three are not limited to a single State. The Central Missouri region yielded a small output, which is combined with that of Southeastern Missouri. The Arbuckle Mountain region of Southern Oklahoma has had no production since 1918. The output by regions in 1942 is given in the following table.

## Mine production of lead and zinc in the Central States in 1942, by regions

	Lea	q ı	Zin	Total	
Region	Short tons	Value	Short tons	Value	value
Concentrates:					
Joplin or Tri-State	44, 857	\$4, 456, 782		\$30, 905, 327	\$35, 362, 109
Southeastern Missouri	277, 255	19, 426, 540	4 1, 739	41,913	19, 468, 453
Upper Mississippi Valley 6	1, 289	119, 026	20,601	1, 207, 275	1, 326, 301
Kentucky-Southern Illinois Northern Arkansas	4,059	262, 984 177	14, 687 518	852, 617 27, 431	1, 115, 601 27, 608
[4] 사람들 마음 아마들이 되는 사람들이 되었다.					, 000
	327, 463	24, 265, 509	481, 342	33, 034, 563	57, 300, 072
Total, 1941	287, 948	19, 342, 323	513, 511	25, 495, 005	44, 837, 328
Recoverable metal:					
Joplin or Tri-State	34, 341	4, 601, 694	237, 936	44, 256, 096	48, 857, 790
Southeastern Missouri	7 197, 432	26, 455, 888	8 842	156, 612	26, 612, 500
Upper Mississippi Valley	908	121,672	11, 126	2, 069, 436	2, 191, 108
Kentucky-Southern Illinois	2, 546	341, 164	8,096	1, 505, 856	1, 847, 020
Northern Arkansas	2	268	181	33,666	33, 934
공급하다 가게하다 하나 하는 내 보다 있다.	235, 229	31, 520, 686	258, 181	48, 021, 666	79, 542, 352
Total, 1941	209, 362	23, 867, 268	276, 006	41, 400, 900	65, 268, 168

1 Includes galena and small quantity of lead carbonate concentrates.

Includes gaiena and smail quantity of lead carbonate concentrates.

2 Includes sphalerite and relatively small quantity of zinc carbonate and silicate concentrates.

3 Includes 180 tons of lead concentrates and 468 tons of zinc concentrates from Central Missouri.

4 Includes 1,260 tons of zinc-lead carbonate averaging 19.52 percent zinc and 2.46 percent lead.

5 Region includes Iowa, Northern Illinois, and Wisconsin; no production in Iowa from 1918 to 1942, in-

6 Includes 141 tons of lead and 179 tons of zinc from Central Missouri.
7 Includes 28 tons contained in zinc-lead carbonate.
8 Includes 450 tons recovered in fuming slag from byproduct copper-lead-zinc matte produced in smelting

Quantity and tenor of copper, lead, and zinc ores, old tailings, etc., produced in some 1 Central States, 1940-42, by States

	19	940	19	141	1942		
State	Ore, etc.	Metal con- tent <sup>2</sup>	Ore, etc.	Metal con- tent <sup>2</sup>	Ore, etc.	Metal con- tent 2	
Kansas Michigan Missouri Oklahoma Wisconsin	Short tons 3, 153, 800 4, 438, 219 6, 457, 400 11, 250, 400 190, 326	Percent 2. 40 1. 02 2. 94 1. 80 3. 61	Short tons 3, 696, 247 4, 282, 448 6, 792, 594 13, 883, 989 211, 973	Percent 2. 55 1. 08 2. 85 1. 52 3. 86	Short tons 3, 872, 052 4, 362, 640 9, 298, 758 12, 798, 423 301, 674	Percent 1. 85 1. 05 2. 63 1. 45 3. 74	
	25, 490, 145		28, 867, 251		30, 633, 547		

1 Only small-scale intermittent mining done in Arkansas from 1918 to 1942; Kentucky and Illinois excluded because part of the metal output (lead and zinc) was a byproduct of fluorspar mining, and the quantity of metal-bearing material hoisted could not be determined.

<sup>2</sup> The percentages represent metal content of the ore insofar as it is recovered in the concentrates. In Michigan the metal so recovered is copper; in other Central States the metals are lead and zinc combined, relative proportions of which are shown in third table of this chapter and in tables of tenor of ore given in sections devoted to the respective States.

## MINING AND METALLURGIC INDUSTRY

Most of the ore mined in the Central States is concentrated by the companies producing it, but that mined by some of the large producing companies in the Tri-State and Upper Mississippi Valley regions is sent to custom mills, which also afford an outlet for crude ore produced by individuals and partnerships working small mines or gouging in large mines abandoned by former operators. The bulk of the ore The bulk of the ore is treated by gravity concentration, supplemented by flotation. 1939 a large tonnage of ore has been treated by the differential-density

THE REPORT OF THE PARTY OF THE

(or sink-and-float) process in the Central mill of the Eagle-Picher Mining & Smelting Co. at Cardin, Okla.; the enriched product resulting from treatment by this process is concentrated further by jigging and flotation. The concentrates produced in the Central States generally have an established market. In 1942 copper concentrates from Michigan were smelted in plants at Hubbell and Houghton. Mich.; lead concentrates from Southeastern Missouri were sent to smelters at Herculaneum, Mo., and Alton, Ill.; and lead concentrates from the Tri-State district went to smelters or pigment plants at Galena and Coffeyville, Kans., Alton and Hillsboro, Ill., Herculaneum, Mo., and Omaha, Nebr. Zinc concentrates from the Tri-State district moved to plants at Bartlesville and Henryetta, Okla.; Coffeyville and Galena, Kans.; Fort Smith and Van Buren, Ark.; Danville, East St. Louis (Fairmont), Hillsboro, and La Salle, Ill.; Donora and Josephtown, Pa.; and Moundsville, W. Va. Most of the lead and zinc concentrates from Wisconsin, Illinois, and other scattered districts in the Central States were shipped to plants that treated the concentrates from the Southeastern Missouri and Tri-State districts. Small tonnages of zinc carbonate from Arkansas and Missouri were shipped to chemical plants at Collinsville, Ill., and Newcastle, Pa.

## REVIEW BY STATES

#### ARKANSAS

The small output of lead and zinc in Arkansas in 1942 came from 33 mines and prospects in Boone, Izard, Lawrence, Marion, Newton, and Searcy Counties. None of the mines was a steady producer, and only 4 shipped as much as a carload of concentrates. The total shipments comprised 485 tons of carbonate and mixed carbonate, silicate, and sulfide averaging 39.50 percent zinc, 33 tons of sulfides averaging 57.10 percent zinc, and 3 tons of lead concentrates averaging 63.33 percent lead. Most of the carbonate produced from January to October was sold in small lots to the Manda Industrial Corporation at Harrison, which shipped it in carlots to the Chemical & Pigment Co. at Collinsville, Ill. The rest of the zinc concentrates were shipped to smelters at Fort Smith and Van Buren, Ark. Small tonnages of concentrates were produced in mills at the Gloria-Alma-Jackpot group near Zinc, Boone County; the Edith, Leader Hollow, and McIntosh near Rush, Marion County; the Bald Hill, Newton County; and the Excelsior and Lone Star, Searcy County. The Silver Hollow group near Rush and the Big Hurricane in Searcy County were reopened for examination through preliminary R. F. C. loans. The Bureau of Mines did 3,368 feet of diamond drilling in the Rush Creek district to explore strata below mining done in the past.

#### ILLINOIS

Northern Illinois (see section on Wisconsin for output data).—All the lead and zinc ores shipped from mines in Northern Illinois in 1942 were sold to the Vinegar Hill Zinc Co. custom mill near Cuba City, Gill Bros. continued to work the old Hughlet and Gray mine near the Illinois-Wisconsin State line and also worked the adjacent North Unity from July through December and the South Unity throughout October. The Hughlet and Gray was shut down February 4, 1943, but the North Unity, on which a 132-foot shaft was sunk in 1942, continued producing good ore. Individuals shipped a few truckloads of ore from Scales Mound and Galena. The Bureau of Mines approved an exploratory drilling project on the Gray property south of Galena and had three churn drills running under contract early in 1943.

Southern Illinois.—From 1939 through 1942 the zinc-lead fluorspar mines of the Mahoning Mining Co. near Cave in Rock, Hardin County, contributed most of the zinc and lead output from Southern Illinois. In 1942 the company operated the W. L. Davis-Deardorff. Green No. 1, and Anna L. Davis mines. The ore is composed chiefly of fluorspar, sphalerite, and galena, which are recovered as separate products in the company 200-ton selective flotation mill at Rosiclare. The fluorspar concentrates produced in 1942 were mostly of acid grade; the sphalerite averaged 62.87 percent zinc, and the galena 63.88 percent lead. A small part of the mill feed was custom ore from other properties in Southern Illinois and Kentucky, mostly fluorspar mines yielding zinc and lead as byproducts. During the year the company sank a 363-foot shaft on the Green No. 1 mine and began sinking another shaft on the Green No. 2; at the end of the year it had six drills at work in a greater effort to discover and extend ore bodies and was installing additional machinery to expand the capacity of the Hillside Fluor Spar Mines continued to ship byproduct lead concentrates. The total output of lead concentrates in Southern Illinois in 1942 was 3,566 tons averaging 63.83 percent lead and about 5.14 ounces of silver to the ton, and that of zinc concentrates was 13,590 tons averaging 62.87 percent zinc. Production (in terms of recovered metals) amounted to 2,211 tons of lead, 104 ounces of silver, and 7,689 tons of zinc, compared with 2,256 tons of lead, 20,340 ounces of silver, and 7,480 tons of zinc in 1941.

#### KANSAS

The Kansas lead and zinc mines are in the Tri-State (Joplin) mining region, embracing parts of Cherokee County, Kans., and Ottawa County, Okla., and about 12 counties in Southwestern Missouri. General details of the Tri-State mining industry are given in following

pages devoted to Southwestern Missouri.

The total output of zinc from Kansas ores and old tailings decreased 22 percent and lead 35 percent in 1942 from 1941. The Baxter Springs-Blue Mound-Treece area extending northward from the Oklahoma-Kansas State line has been the principal producing area since 1918; it yielded 96,856 tons of zinc concentrates and 12,183 tons of lead concentrates in 1942 compared with 122,582 and 18,835 tons, respectively, in 1941 (revised figures), and an annual average of 122,024 and 18,973 tons from 1918 through 1940. In 1942 the output of both zinc and lead from the Eagle-Picher Mining & Smelting Co. Westside-Barr and Webber mines was less than in 1941, and the total output of the Big John, Black Eagle, Chubb, Mid-Continent, Wilbur, and Robob mines shipping to the Central mill at Cardin, Okla., decreased. The Webber mill was closed in October, and the ore from the Webber lease was diverted to the Central mill. Two shafts on the lease north and northwest, respectively, of the Webber mill shaft were reopened, and spur tracks connecting them with the railroad to the Central mill were built. A shaft on the Foley land was reopened

to facilitate mining of the Westside ore, and the old Westside mill shaft was being converted for double-skip hoisting in conjunction with the erection of a 1,000-ton hopper. Other new Eagle-Picher operations in Kansas included reopening of the Lucky Jew Parmenter and Velie Leopard properties. In November the company also began preparing to reopen the Paxson mine and 2,400-ton mill as agent for the Metals Reserve Co. This mine began producing in April 1943.

The 1,800-ton Ballard central mill of the St. Louis Smelting &

Refining Co. was operated at approximate capacity throughout 1942 on company ore from the Ballard, Bailey, Clark, English "O", Keith, Shanks, Slaughter, and Walter H. mines; the output of zinc concentrates was less than in 1941, but that of lead concentrates was approximately the same in both years. The Bilharz Mining Co. operated the Bilharz-Brewster mine throughout 1942, treating the ore in the company mill which also handled crude ore from the L. D. Brewster and Huttig mines in Oklahoma from January to July. The Madison mill was run steadily on ores from the Peru-Banning group and Craig and Brugger leases. The Wade custom mill treated 20,817 tons of mine dirt from the Discard, Commonwealth, and other small mines in Kansas and Oklahoma. From September through December the Mineral Products Co. shipped crude ore from a shaft on the Swalley property to the Mission mill in Oklahoma. The Pilot mill was shut down in March and remained idle the rest of the year. The Oldham Mining Co. shipped ore to custom mills. The Dines Mining Co. continued to run its mill on company and custom ores, mostly from the Southern, Harris, and Hartley No. 1 mines. The Beck No. 3 mill at Baxter Springs was reconditioned to treat company and custom ores and was put in operation in January 1943; part of the ore treated came from the McArthur mine, on which two shafts were sunk in The Muncie mill of the Federal Mining & Smelting Co. was closed in April, and the ore from the Muncie-Tar Creek-Semple group was then sent to the company Gordon central mill in Oklahoma, which also treated other Kansas ore from the Federal Jarrett mine. The north shaft on the Muncie was reopened and reequipped for additional development. The Muncie mill and the remaining part of the old Jarrett mill were dismantled and salvaged. The Harris Mining Co. continued to work the Robinson mine and in October began mining ore from a new shaft on the Silver Fox lease. The ore from these two mines and that from the leased Evans-Wallower No. 24 was concentrated in the Youngman mill. The Opperman mine, operated by the Lula Bell Mining Co., was closed in August. The New Blue Mound Mining Co. operated one section of its mill on crude ore from the Blue Mound mine, and the Worley Mining Co. operated the other section on new tailings from the Blue Mound ore and old tailings hauled from scattered piles in the vicinity. The Captain and Early Bird tailing mills were run steadily, and their output of zinc concentrates was larger than in 1941.

The Kansas part of the Waco district yielded 5,113 tons of zinc concentrates and 5 tons of galena in 1942 compared with 8,361 and 15 tons, respectively, in 1941. The St. Louis Smelting & Refining Co. operated its No. 9 mill (capacity 800 tons in 16 hours) throughout 1942. More than half the ore treated came from the company Olsen and High Five leases in the Missouri part of the Waco district; the rest came from the company Grasselli and J. M. Bennett leases, the Stotts City Mining Co. J. M. Bennett lease, and the Beck Mining Co. Hurlbut lease. The F. W. Evans mill treated ore from the O'Neill land (partly in Kansas and partly in Missouri), the St. Louis Smelting & Refining Co. land, and the Blue Rock mine in Missouri. In the Galena area, formerly (1876–1917) the principal zinc- and lead-producing area in Kansas, the Eagle-Picher Mining & Smelting Co. continued churn drilling, sank two new shafts and reopened several old shafts, and did underground development work and pumping. Ore shipments to the company Bird Dog mill in Oklahoma began in March 1943. The Galena Mining Co. shipped crude ore from the Southside mine to the Central mill.

Mine shipments of lead and zinc in Kansas, 1938-49

				70 S		Metal content 1					
Year	Mines produc-	Tead co	oncentrates Zinc		Zinc concentrates		Lead		Zina		
	ing	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value		
1938	31 30 34 58 81	19, 909 17, 845 13, 424 18, 888 12, 253	\$1, 023, 851 1, 010, 106 907, 296 1, 264, 147 1, 167, 302	138, 546 126, 235 105, 070 131, 406 103, 247	\$4, 132, 248 4, 300, 365 4, 420, 860 6, 595, 506 6, 926, 745	15, 239 13, 697 11, 927 14, 538 9, 419	\$1, 401, 988 1, 287, 518 1, 192, 700 1, 657, 332 1, 262, 146	73, 024 68, 971 57, 032 71, 403 55, 874	\$7, 010, 304 7, 172, 984 7, 186, 032 10, 710, 450 10, 392, 564		

<sup>1</sup> In calculating metal content of the ores from assays allowance has been made for smelting losses of both laad and zinc. In comparing the value of ore and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead and zinc is calculated from the average price for all grades.

Tenor of lead and zinc ore and old tailings milled and concentrates produced in Kansas, 1941–42

	19	<b>141</b>		1942
	Crude ore	Old tailings	Crude ore	Old tailings
Total ore and old tailings milledshort tons_ Total concentrates produced:	2, 446, 207	1, 250, 040	2, 170, 121	1, 701, 931
Galenado	18, 886	2	12, 253	[
Sphaleritedo Ratio of concentrates to ore, etc.:	123, 000	8, 406	92, 540	10, 70
Leadpercent_	0.77		0. 56	
Zincdo	5.03	0.67	4. 26	0. 6
Metal content of ore, etc.: 1 Leaddodo	. 61		. 44	
Zincdo	3.04	.40	2, 57	. 3
Average lead content of galena concentratesdo	78. 54	50.0	78. <b>44</b>	
Average value per ton:	60. 48	58.9	60. 38	57.9
Galena concentrates	<b>\$66.93</b>	\$56.00	<b>\$</b> 95. <b>27</b>	
Sphalerite concentrates	50. 32	48.38	65. 55	\$80.4

<sup>&</sup>lt;sup>1</sup> Figures represent metal content of the crude ore (or "dirt") only insofar as it is recovered in the concentrates; data on tailing losses not available.

#### KENTUCKY

Part of the Kentucky output of zinc and most of the lead in 1942 were byproducts of fluorspar mining. The United States Coal & Coke Co. Fluorspar Division, operating the Lafayette mine near Mexico, was the principal shipper of byproduct zinc concentrates and also shipped lead concentrates. The largest shipper of lead con-

THE WASHINGTON TO SEE THE PROPERTY OF THE PROP

centrates was the Kentucky Fluor Spar Co., which recovered the concentrates in milling fluorspar from the Babb mine. The Cumberland Fluorspar Co., Delhi Foundry Sand Co., and Summers Fluorspar Mine shipped zinc-lead fluorspar ore to the Mahoning mill at Rosiclare, Ill. The Cumberland Fluorspar Co. also shipped 530 tons of carbonate ore averaging 30.62 percent zinc to oxide plants. During November and December the Eagle-Picher Mining & Smelting Co. shipped 1,220 tons of crude zinc-lead sulfide ore from its Nunn mine 6 miles east of Marion to the company Central mill at Cardin, Okla. The total State output of recoverable zinc was 407 tons and that of lead 335 tons compared with 427 and 282 tons, respectively, in 1941. The Twin Valley Mining Co. continued developing the Gratz mine in Owen County and installed additional equipment in the mill, increasing its capacity (formerly 50 tons daily) to 100 tons. Mining and milling of ore were begun in February 1943.

#### MICHIGAN

Although the output of refined copper in Michigan decreased 2 percent in 1942 from 1941, there was a material expansion in 1942 in the scope of mining and development operations by the mining companies. Special arrangements with Federal procurement agencies in the latter part of 1941, whereby the copper produced from certain "high-cost" mines would be paid for on a cost-plus basis, and the premium-price plan placed in effect in February 1942 enabled the companies to make preparations to mine and mill copper-bearing rock not commercial under the ceiling copper price of 12 cents a pound. The average grade of the crude ore mined was 10 percent lower than in 1941, and that of old tailings (sands) treated at reclamation plants was slightly lower. The total crude ore treated increased from 1,741,961 tons in 1941 to 1,952,781 tons in 1942; tailings decreased from 2,540,487 to 2,409,859 tons. The tailings yielded 34 percent of the total copper in 1942 and 36 percent in 1941.

The concentrate ("mineral") produced at mills in Michigan in 1942 was smelted at plants of the Calumet and Hecla Consolidated Copper Co. at Hubbell and the Copper Range Co. at Houghton. Some of the copper bullion was cast into anodes and shipped to the electrolytic refinery at Laurel Hill, N. Y., where silver was recovered. Silver was also recovered by hand-picking at the mine and from some

of the concentrates.

Mine production of silver and copper in Michigan, 1938-42 1

			Copper 2		Concen	trate		
Year	Silver		Yie	ld	("miner	Ore ("rock")		
1 631	(fine ounces)	Pounds	Pounds per ton of ore ("rock")	Percent	Pounds	Yield (percent copper)	(short tons) 4	
1938 1939 1940 1941	93, 634 101, 878 88, 657 60, 796 61, 674	93, 486, 000 87, 970, 000 90, 396, 000 92, 880, 000 91, 358, 000	24. 9 19. 1 20. 4 21. 7 20. 9	1. 24 . 96 1. 02 1. 08 1. 05	144, 964, 890 136, 771, 339 138, 451, 495 141, 100, 268 141, 372, 582	64. 5 64. 3 65. 3 65. 8 64. 6	3, 757, 705 4, 603, 751 4, 438, 219 4, 282, 448 4, 362, 640	

<sup>&</sup>lt;sup>1</sup> Figures based upon actual recovery of copper from "mineral" smelted and estimated recovery from "mineral" not smelted during year.

<sup>2</sup> Includes copper from sands.

<sup>3</sup> Includes "mineral" from sands.

<sup>4</sup> Includes sands.

Value of silver and copper produced in Michigan mines, 1938-42

		Cop	per				Cop	per	
Year	Silver	Total	Per ton of ore ("rock") and sands	Total	Year	Silver	Total	Per ton of ore ("rock") and sands	Total
1938 1939 1940	\$60, 531 69, 154 63, 045	\$9, 161, 628 9, 148, 880 10, 214, 748	\$2, 44 1, 99 2, 30	\$9, 222, 159 9, 218, 034 10, 277, 793	1941 1942	\$43, 233 43, 857	\$10, 959, 840 11, 054, 318	\$2. 56 2. 53	\$11, 003, 073 11, 098, 175

The Calumet and Hecla Consolidated Copper Co. continued to be the largest producer of copper in Michigan. After June 1, 1942, when the company purchased all the physical assets of the Wolverine Tube Co. (manufacturer of seamless nonferrous tube) at Detroit, the mining, smelting, and other company operations in Northern Michigan were operated as the Calumet Division, and the newly acquired enterprise became the Wolverine Tube Division. The producing company mines in 1942 were the Ahmeek, Peninsula, Douglass, and No. 4 North Kearsarge groups. The ore from all four groups was treated in the 6,800-ton Ahmeek stamp mill by gravity concentration followed by flotation of the fines. The details of operations at the mines that follow were extracted from the annual company report to stockholders. Operations at the Ahmeek mine were confined largely to stoping. Exploration of the Peninsula area was continued throughout the year. A heavy program of dead work, consisting of the extension of No. 4 shaft, reopening of three old levels, and unwatering old Seneca workings, resulted in high costs for the copper produced. No important new ore shoots were discovered, but the extension of two known ore shoots was determined. At the Douglass group a total of 6,228 feet of openings was driven from No. 2 and No. 3 Ahmeek shafts. A large portion of the openings was in low-grade vein, but a reasonable percentage was in ground of probable commercial value. The No. 4 North Kearsarge mine was reopened and operated under a contract with the Metals Reserve Co. During February and March the surface plant and underground openings were rehabilitated; production started in April at a moderate rate and increased gradually throughout On the Iroquois property a surface plant was constructed, an exploratory inclined shaft was sunk to a depth of about 700 feet, and 196 feet of drifting was done at the 600-foot level. At the Central property underground workings were unwatered, the surface plant was repaired, diamond drilling was done, the shaft was sunk 128 feet below the 200-foot level, and crosscutting to the mineralized area was begun.

のでは、100mmのでは、100mmのでは、100mmのでは、100mmのでは、100mmのでは、100mmのでは、100mmのでは、100mmのでは、100mmのでは、100mmのでは、100mmのでは、100mmので

Both the Lake Linden and the Tamarack dredges operated in the older, richer parts of the respective deposits adjacent to the original shore lines. At Lake Linden the conglomerate tailings above the water line will have disappeared before the end of the coming summer, and operations thereafter will be spotty and irregular until reserves are exhausted. The profitable life of this asset is short. At Tamarack there is some promise of an extended life on amygdaloid tailings if a suitable price can be obtained for the copper produced.

Copper output from the Champion and Globe mines of the Copper Range Co. increased in 1942. The ore from both mines was treated

はいいは、これには、これのではないのではないのでは、これがないというというないというというないとなっているというないというできないというというというというというというというというというというというというと

in the company mill at Freda. Copper recovered from 355,630 tons of mine ore and 223,859 tons of sands treated in the tailings-recovery plant totaled 18,441,607 pounds. The average yield of fine copper per ton of mine rock was 49.97 pounds compared with 52.38 pounds in 1941. Mine workings include two 70° shafts about 5,000 feet deep and one subshaft about 400 feet deep. Development work done during the year totaled 198 feet of shaft, 12,086 feet of drifts and crosscuts, and 12,571 feet of diamond drilling. The concentrates were smelted in the company smelter, which also handled custom concentrates from the mills of the Isle Royale Copper Co. and the Quincy Mining Co.

The Isle Royale Copper Co. mine and 2,000-ton stamp mill were run continuously in 1942. Crude ore produced totaled 315,142 tons compared with 316,598 in 1941. The yield of fine copper per ton of rock averaged 20.16 pounds in 1942 and 21.223 in 1941. The 1942 annual company report to stockholders stated that mining costs were gradually increasing and that notice had been received in February 1943 of an increase in wages awarded by the Nonferrous Metals Commission; the notice indicated that some increase in the copper price would be necessary to enable the company to pay the wage

increase.

The Quincy Mining Co. operated its mine and mill continuously in 1942. Both the tonnage of rock treated and the yield of copper per ton were slightly lower than in 1941. In 1942 the company obtained a loan of \$1,150,000 from the Metals Reserve Co. to be expended in constructing a 4,000-ton plant for re-treating the Quincy Mining Co. tailing deposit at Mason, on Torch Lake. The loan is to be retired by payment of 4 cents per pound of copper produced. The plant will be constructed by the Calumet and Hecla Consolidated Copper Co. which will furnish much of the machinery from dismantled structures no longer needed by that company. After completion, the plant will be operated by the Quincy Mining Co. All the copper produced will be sold to the Metals Reserve Co. for 17 cents a pound.

From January through December 1942 Arcadian Mines (incorporated May 2, 1942) drove 1,250 feet of development drifts and 150 feet of crosscuts on the company property on the south side of Ripley Hill. The Ripley adit, through which the property is being developed, was 2,050 feet long at the end of the year. About 250 tons of ore removed in drifting were stored for a mill test, and nearly a ton of

native ("mass") copper was sent to the Copper Range smelter.

## MISSOURI

In 1942 Missouri maintained by a wide margin the rank it has held for 35 years as the chief lead-producing State. Under the stimulus of heavy demand and higher prices brought on by the war, the output of zinc increased 73 percent in 1941 over 1940 and 66 percent in 1942 over 1941. Lead production increased 20 percent in 1942 over 1941. The lead comes largely from the Southeastern Missouri region and the zinc mostly from Southwestern Missouri. In 1942 silver, copper, and zinc were recovered in relatively small quantities as byproducts in smelting and refining lead concentrates from Southeastern Missouri. The Central district of Missouri produced 141 tons of recoverable lead and 179 tons of zinc in 1942; these figures are combined with those of Southeastern Missouri in the table that follows.

# Mine production of lead and zinc in Southeastern and Central Missouri, 1938-42

	Lead co	ncentrates	Zince	oncen-		Metal con	tent 1	
Year		lena)	trates	(sphal- te)	I	.ead	Zinc	
	Short tons	Value <sup>2</sup>	Short tons	Value	Short tons	Value	Short tons	Value
1938	163, 500 210, 526 232, 871 228, 572 277, 255	\$9, 040, 593 12, 339, 360 14, 269, 600 15, 404, 226 19, 426, 540	3 815 4 5, 192 5 1, 739	\$20,000 73,202 41,913	118, 870 153, 522 169, 908 164, 388 197, 432	\$10, 936, 040 14, 431, 068 16, 990, 800 18, 740, 232 26, 455, 888	233 1, 100 6 842	\$29, 358 165, 000 156, 612

<sup>&</sup>lt;sup>1</sup> In calculating metal content of the ores from assays allowance has been made for smelting losses of both lead and zinc. In comparing the values of ore and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead and zinc is calculated

from the average price for all grades. 2 Values given are to a certain extent arbitrary, as part of the lead concentrates are smelted by the producer.

3 Includes 500 tons of zinc carbonate ore containing 106 tons of recoverable zinc.

4 Includes 4,720 tons of zinc-lead carbonate concentrates containing 893 tons of recoverable zinc and 172

28 tons of lead.

6 Includes 450 tons recovered in fuming slag from byproduct copper-lead-zinc matte produced in smelting lead concentrates.

Tenor of lead ore and concentrates in Southeastern Missouri disseminated-lead district, 1938-42

The second secon

	1938	1939	1940	1941	1942
Total lead oreshort tons_Galena concentrates in orepercent_Zinc content of oredoAverage lead content of galena concentratesdoAverage value per ton of galena concentratesdo		5, 127, 000 4, 11 (1) 74, 4 \$58, 61	5, 837, 400 3.99 (1) 74, 45 \$61, 28	5, 737, 230 3, 98 (1) 73, 31 \$67, 39	7, 107, 191 3. 90 (1) 72. 65 \$70. 04

<sup>1</sup> Figures not available.

# Mine production of lead and zinc in Southwestern Missouri, 1938-42

	Lead concentrates			Zinc concentrates				Metal content 1				
Year	Ga	lena	Carbo	onate	Sphalerite		Silicate		Lead		Zine	
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short	Value
1938 1939 1940 1941 1942	4, 130 3, 674 2, 818 2, 084 2, 790	158, 556 125, 730		\$3, 100 2, 446 4, 379 864	27, 741 22, 917 38, 513	944, 587	949 807 1, 277	10, 965 14, 355	2, 759 2, 144 1, 521	214, 400	15, 096 12, 470 20, 832	\$981, 69 1, 569, 98 1, 571, 22 3, 124, 80 6, 612, 67

<sup>&</sup>lt;sup>1</sup> In calculating metal content of the ores from assays allowance has been made for smelting losses of both lead and zinc. In comparing the values of ore and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead and zinc is calculated from the average price for all grades.

<sup>§</sup> Includes 1,271 tons of zinc and zinc-lead carbonate concentrates containing 213 tons of recoverable zinc and

The state of the s

Tenor of lead and zinc ore and old tailings milled and concentrates produced in Southwestern Missouri, 1941-42

	1	941	1942		
	Crude ore	Old tailings and slimes	Crude ore	Old tailings and slimes	
Total ore, etc., milledshort tons_ Total concentrates produced:	777, 351	252, 603	1, 404, 731	751, 25	
Leaddo	2, 147	27	2,773	3'	
Zincdo	37, 594	2, 196	59, 909	8, 48	
Ratio of concentrates to ore, etc.:		Market No.			
Leadpercent_	0. 28	0.01	0. 20	0.00	
Zincdo	4.84	.87	4. 26	1.1	
Metal content of ores, etc.: 1					
Leaddo	. 20	. 006	. 15		
Zinedo	2.83	. 47	2. 48		
verage lead content of galena concentrates_do	72.8	51.9	77. 1	64.	
Average lead content of lead carbonatedo	52. 22		50.0		
Average zinc content of sphalerite concentrates do Average zinc content of silicates and carbonates	59. 74	53.82	58. 12	55. 5	
percent.	22, 47		23, 25		
verage value per ton:	24. 41		20. 20		
Galena concentrates	\$60, 62	\$38. 52	\$108.30	\$105. 1	
Lead carbonate concentrates	48. 66	ψ03. 02	43. 20	φ100.	
Sphalerite concentrates	50. 34	43, 45	69. 79	74.7	
Zinc silicates and carbonates	11. 24		15. 85		

<sup>&</sup>lt;sup>1</sup> Figures represent metal content of the crude ore (or "dirt") only insofar as it is recovered in the concentrates; data on tailing losses not available.

Southeastern and Central Missouri.—The disseminated-lead district of Southeastern Missouri yielded 197,291 tons of recoverable lead in 1942—an increase of 32,949 tons (20 percent) over 1941. The bulk of production in 1942, as in the past, came from St. Francois County, where the St. Joseph Lead Co. operated continuously its four groups of mines and four mills, comprising the Bonne Terre, Leadwood, Desloge, and Federal Divisions. The mines were operated two 8-hour shifts per working day and the mills three 8-hour shifts, and all worked 6 days a week. Ore hoisted per day averaged 21,100 tons, which kept the mills operating at capacity. One ore-hoisting shaft is at each mill; in addition, there were 11 operating shafts equipped for handling men, supplies, and poor rock. The average depth of the four ore-hoisting shafts is 440 feet. The ore occurs in extensive, flatlying deposits in limestone and is mined from open stopes supported by pillars. Electric-powered mechanical loaders and locomotives are used for loading and underground haulage. Mine development and drilling done in 1942—77,143 feet of drifts, a 716-foot raise, 9,564 feet of churn drilling, and 2,305,272 feet of diamond drilling—were nearly double the total in 1941. New equipment purchased included 6 diamond core drills, 12 underground mechanical loaders, 100 mine cars, and 24 underground trolley locomotives. The annual company report to stockholders for 1942 stated that although the mines were still being worked beyond their economic capacity the development work during the year was very satisfactory, and the tonnage of proved ore was greater than it had ever been. In Madison County production of lead from the Mine La Motte mine of the Mine La Motte Corporation (50-percent owned by the St. Joseph Lead Co.) also increased. The 1,000-ton mill was enlarged during the latter part of 1942 to provide 500 tons additional daily capacity to treat the chat tailings from old operations. Mine development and drill prospecting done totaled 3,451 feet of drifts and 41,026 feet of churn

drilling. The Fredericktown Lead Co., which had purchased the mining leases on the Catherine and Fleming tracts and the 400-ton Clark and Hallock mill, installed a new Diesel power plant, surface buildings, and mining equipment and in March began treating ore from the reopened Catherine mine. During the rest of the year 96,763 tons of ore were treated, yielding 2,470 tons of 76-percent lead concentrates. Of the 277,075 tons of lead concentrates made in 1942 in Southeastern Missouri, about 129,560 tons were flotation concentrates. The St. Louis Smelting & Refining Co. carried on prospect drilling and mine-development work at its own property and the adjoining leased property of the Missouri Cobalt Co. at Fredericktown; the commercial metals in the ore are lead, copper, nickel, and cobalt. The ore was tested in the Bureau of Mines laboratory at Rolla to develop a suitable treatment process.

The zinc ore and concentrates shipped from Southeastern Missouri in 1942 were carbonates, mostly from old dumps on the Valle Mining Co. properties in Jefferson and St. Francois Counties and the Frumet mine on the Tausig estate west of DeSoto. Shipments totaled 1,271

tons, averaging 19.76 percent zinc and 2.44 percent lead.

In Central Missouri the Wemhaner Mining Corporation continued to mine zinc, lead, and coal from its leased open-pit mine on the Monarch Coal & Mineral Co. land in Moniteau County. In treatment, the coal and some waste are removed by screens and coal jigs, and the ore rock is then concentrated further in ore jigs. Otis and E. M. Sullens worked the Lowery mine near Enon on a small scale and shipped 150 tons of galena averaging 80 percent lead. A 2-ton lot of lead ore was shipped from Lynn Creek.

Southwestern Missouri.—The method of marketing the mine output in the Tri-State or Joplin lead and zinc region (Southwestern Missouri, Kansas, and Oklahoma) is explained in the reports of this series for

1940 and 1941.

The total value given in this report for all concentrates produced in the Tri-State region is based upon actual receipts by the sellers and not upon quoted prices. Under the ceiling price of 8.25 cents a pound for slab zinc at East St. Louis, the quoted price for zinc concentrates at Joplin remained at \$55.28 a ton throughout 1942. The quoted price for galena opened in January at \$68.64 a ton on a metal contract basis; on January 13 it was raised to \$76.75, which held until March 28 when the price was reduced slightly to \$76.54; it remained

at that level the rest of the year.

Effective February 1, 1942, the Metals Reserve Co. paid premiums of \$28.05 a ton for 60-percent zinc concentrates and \$39.60 for 80-percent galena for production from individual mines in excess of quotas fixed jointly by the War Production Board and the Office of Price Administration. On December 1 the premiums were increased slightly to \$29.70 a ton for zinc concentrates and \$41.80 for galena following a revision of the formula used in determining the recoverable-metal content of the concentrates; the recovery factor for zinc was raised from 85 to 90 percent and that for lead from 90 to 95 percent.

Early in 1943 the scope of the premium-payment program was broadened to afford an additional premium for lead (called "B"-level quota) and an additional premium or premiums for zinc (called "B" and "C" level) at operations where such additional premiums were considered essential to insure maximum necessary mine pro-

THE REPORT OF THE PARTY OF THE

大学をなるというながないという

The premium payments on the "B"-level quota were twice those on the original or "A" level, and the payment on the "C" level (zinc only) was three times that on the "A" level. The maximum combined commercial price and premiums obtainable for standardgrade zinc concentrates was therefore \$144.38 a ton and for lead concentrates \$160.14.

All Government premium payments for zinc and lead produced from restricted Indian lands in 1942 were subject to royalties, at rates (usually 10 percent) specified in the leases, for money received from sales at market prices. Lessees on other lands with one or two exceptions also paid part of the premium moneys received as royalty. April 1943 the Office of Price Administration issued Maximum Price Regulation 356 freezing royalties on April 1 at rates in effect December Under this regulation, "B"- and "C"-level premiums are not subject to royalties.




FIGURE 1.—Average prices received by sellers per ton of concentrates in the Tri-State district, 1907-42.

Local mining companies did much prospect drilling and other exploration and development work in 1942. The total number of drill rigs in operation rose from 67 on March 31 to 99 on June 30 and 100 on November 1. About 21 new shafts (averaging 190 feet deep) were sunk during the year, and at least 43 old shafts were reopened; reopenings, however, were partly offset by closings. Progress was made in mechanizing underground loading, and by the end of the year about 50 drags and more than 100 other types of mechanical loaders were being used in the district. Labor shortages, which became acute for some operators during the summer and early fall, were somewhat ameliorated later in the year. In general, established mines and mills were able to obtain needed supplies and replacement equipment under assigned priority ratings, although there was delay at times in getting

delivery of steel products, lumber, and electrical equipment. The Reconstruction Finance Corporation granted loans for development and mining on about 15 Tri-State properties, and the Bureau of Mines investigated 34 properties and did churn drilling on the Townsite mine at Cardin, Okla.




FIGURE 2.—Quantity of crude ore milled in the Tri-State district, 1907-42.




FIGURE 3.—Metals recovered per ton of crude ore (rock) milled in the Tri-State district, 1907-42.

THE REPORT OF THE PARTY OF THE

Production of zinc in Southwestern Missouri again increased in 1942 and was the highest annual since 1918. The Oronogo Circle open-pit mine at Oronogo continued to be the largest producer. ore is mined by the Oronogo Mutual Mining Co. and milled by the Eagle-Picher Mining & Smelting Co. Under a program undertaken in July to expand production, the rate of ore extraction was stepped up beyond the capacity of the mill on the property, and part of the crude ore was diverted to other Eagle-Picher mills in Oklahoma and Missouri. The rock milled totaled 287,680 tons; in addition, 295,520 tons of waste rock and overburden were removed from the pit, which was 230 feet deep at the end of 1942. The Fenix & Martin Mining Co. continued to operate the La Tosca mine and 200-ton mill, and Fenix & Sons shipped crude ore from a shaft on the Oronogo Mutual property to the Central mill in Oklahoma. Kansas Explorations, Inc., operated its Snapp mine and 600-ton mill near Oronogo throughout the year; the company also reopened the old A. W. C. property near Joplin and equipped it with a 1,000-ton mill, which was put in operation in October. The Eagle-Picher mines served by the Navy Bean mill near Wentworth made a large output in 1942. The Federal Mining & Smelting Co. operated six shafts (average depth 170 feet) on its Granby-American property, treating the ore in the company 1,200-ton mill; the company also developed its Granby-Davis lease, which began producing in September, and nearly completed a large mill at its Duenweg mine. The new mill and the Duenweg mine were placed in operation about April 1, 1943. The American Zinc, Lead & Smelting Co. drilled out a good ore body on the Henckle and Smith lands near Duenweg in 1942 and began developing it by sinking three shafts; the mine was put in operation late in March 1943, and the ore produced was treated on a contract basis in the new Federal mill at Duenweg. The company also struck good ore at Aurora while drilling on the McLain-Jones land and began constructing a mill on the property in March 1943.

The principal producer near Joplin was the Missouri Mining Co. 1,200-ton tailing mill at Chitwood. The High Grade Mining Co. reopened its mine and mill in May and operated until November; the property was then idle until March 1943, when it was put in operation by the Southside Mining Co. The Northside Mining Co., which had its ore milled in the High Grade mill in 1942, built a mill on the Northside property and began milling in January 1943. The St. Louis Mining & Milling Co. operated its custom mill at Thoms Station steadily, affording milling facilities for small mines operating nearby. At Waco the St. Louis Smelting & Refining Co. worked its High Five and Olsen leased mines and sent the ore to the company No. 9 mill across the State line in Kansas. F. W. Evans Mines operated the O'Neill and Blue Rock mines and treated the ore in the company mill in Kansas. C. C. Playter ran his mill (capacity, 12½ tons an hour) continuously on ore from his Reynolds lease at Waco and other ores from small mines near Carl Junction, Joplin, Neck City, and Pleasant Valley and from Galena, Kans. At Webb City the Sciota Milling Co. mill ran steadily on tailings from the Connor Investment Co. land and other properties. Early in 1943 Cooley Bros. began stripping operations with draglines and bulldozers on the F. W. Evans land in Sucker Flat. At Stotts City the Capital Mining Co. continued to operate its Capital mine and in July purchased the adjacent Stotts City Mining Co. property; the ore from both mines was treated in the Capital mill. The Harris Mining Co. mill north of Aurora was run intermittently. Near Ozark, Christian County, the Mary Arnold mine and mill were operated from January through October, and the Monark Mining Co. property was under development and made a small output early in the year. The Wentworth Mining & Milling Co. operated the Kline mine and mill after July. The Southwest Mining Co. began developing its property at Stark City and nearly completed a 250-ton mill before the year ended. Eleven small mills in the Alba-Neck City, Carthage, Duenweg, Granby, Joplin, and Webb City areas produced some concentrates in 1942, mostly from tailings. Zinc carbonate and silicate shipped from scattered mines and dumps in Southwestern Missouri in 1942 (including low-grade zinc-lead concentrates from Granby dump material treated in the Goade mill) totaled 1,510 tons averaging 23.25 percent zinc and 3.58 percent lead.

#### OKLAHOMA

General details of mining and milling in the Tri-State region—which includes northeastern Oklahoma—are given in the preceding pages on Southwestern Missouri. Although Oklahoma continued to yield much the largest part of the total Tri-State production of both zinc and lead, the State output of recoverable lead decreased 9 percent and zinc 12 percent in 1942 from 1941. The total value of the zinc and lead concentrates, however, increased 26 percent owing to the advance in average market prices and the payment by the Government of premiums for over-quota production. About 141 mines produced during the year and 26 mills were operating at the end of the year compared with 120 and 27, respectively, in 1941.

Mine shipments of lead and zinc in Oklahoma, 1938-42

			Pi		Metal content 1				
Year	Lead concentrates		Zinc concentrates		Lead		Zinc		
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	
1938	27, 608 36, 422 27, 913 32, 628 29, 794	\$1, 446, 058 2, 189, 077 1, 656, 497 2, 202, 876 2, 985, 285	208, 484 258, 214 300, 984 307, 207 272, 209	\$6, 390, 422 8, 937, 554 12, 672, 186 15, 427, 235 19, 163, 622	21, 004 27, 720 21, 240 25, 021 22, 806	\$1, 932, 368 2, 605, 680 2, 124, 000 2, 852, 394 3, 056, 004	112, 924 140, 379 162, 935 166, 602 146, 510	\$10, 840, 70 14, 599, 410 20, 529, 810 24, 990, 300 27, 250, 860	

<sup>&</sup>lt;sup>1</sup> In calculating metal content of the ores from assays allowance has been made for smelting losses of both lead and zinc. In comparing the values of ore and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead and zinc is calculated from the average price for all grades.

Tenor of lead and zinc ore, old tailings, and slimes milled and concentrates produced in Oklahoma, 1941-42

	1	941	1942		
	Crude ore	Old tailings and slimes	Crude ore	Old tailings and slimes	
Fotal ore, etc., milledshort tons_ Fotal concentrates produced:	4, 868, 021	9, 015, 968	5, 012, 485	7, 785, 938	
Galenado	32, 296	332	29, 371	• 42	
Sphaleritedo	243, 773	63, 434	226, 302	45, 90	
Ratio of concentrates to ore, etc.:			,		
Leadpercent	0.66	0.004	0.59	0.00	
Zincdo	5. 01	.70	4, 51	.5	
Metal content of ore, etc.: 1					
Leaddo	. 52	.002	. 46	.00	
Zincdo	3.03	.41	2.71	.3	
Average lead content of galena concentrates do Average zinc content of sphalerite concentrates	78. 53	51. 51	78. 43	55. 0	
percent	60. 59	58.97	60.11	58. 2	
verage value per ton:	. 777				
Galena concentrates	\$67.75	\$44.79	\$100.52	- \$77. 8	
Sphalerite concentrates	50, 55	48.94	68, 54	79. 8	

<sup>&</sup>lt;sup>1</sup> Figures represent metal content of the crude ore (or "dirt") only insofar as it is recovered in the concentrates; data on tailing losses not available.

In 1942 the Eagle-Picher Mining & Smelting Co. was again by far the largest producer of both lead and zinc in Oklahoma and in the Tri-State region. The company 13,000-ton Central mill at Cardin treated a total of 3,599,087 rock tons of company and custom ore, of which 2,905,220 tons (81 percent) came from Oklahoma mines, compared with 3,311,144 tons in 1941, of which 2,711,212 tons (82) percent) came from Oklahoma. The concentrating equipment of the mill includes, besides the usual jigs, flotation machines, and tables, a large primary heavy-density (or sink-and-float) cone unit and a smaller secondary cone which provide preliminary stages of concentration at coarse sizes for a large portion of the mill feed. Companyoperated mines in Oklahoma shipping to the mill in 1942 were the Blue Goose Nos. 1, 2, and 3, Crawford, Crystal No. 1, Crystal-Central, Eagle-Picher Gordon Nos. 1 and 2, Grace Walker Nos. 1 and 2, Goodeagle Nos. 1 and 3, Hum-bah-wat-tah Nos. 1, 2, and 3 (includes Jaybird), John Beaver Nos. 1 and 2, Little Greenback, Mehunka, Netta, Niday No. 1, See Sah, Southside Nos. 1 and 2, Stanley, and Wesah Greenback. The Crawford, Goodeagle Nos. 1 and 3, Mehunka, Niday No. 1, Netta, and Southside Nos. 1 and 2 (closed in May 1941) were reopened during the year. The Crawford and Gordon No. 1 were shut down in October and July, respectively, owing to exhaustion of ore; the John Beaver No. 1 was shut down in May because the property was too low-grade to work. New shafts were sunk on the Beck Robinson, Goodeagle No. 3, and Niday No. 1 properties. The Eagle-Picher 2,400-ton Bird Dog mill was not run in 1942 but was reopened in March 1943 and began treating ores from Oronogo, Mo., and Galena, Kans.

The principal shippers of Oklahoma custom ore to the Central mill in 1942 were the American Development Co. (Hunt mine), Baird Mining Co. (American-Douthat), Cameron & Henderson (Admiralty), Cortez-Childress (Jeff City), Davis-Big Chief Mining Co. (Eudora-Whitebird, Imbeau, and Skelton), F. W. Evans (Shorthorn, Tom L.), Lula Bell Mining Co. (Anna Beaver), Mahuska Mining Co. (Acme),

M. & M. Mining Co. (LaSalle, Piokee, Swift, Whitebird), and Mutual

Mining & Development Co. (Slim Jim).

The Federal Mining & Smelting Co. operated its 1,700-ton Gordon central mill throughout 1942 on company ore from the Gordon, Howe, Lucky Bill, Lucky Syndicate, and Quapaw-Davenport mines in Oklahoma and the Federal Jarrett and Muncie groups in Kansas; the mill, built in 1937, operated until March 7, 1943, when it was destroyed by fire. The mines served by the mill were closed, and no announcement was made immediately regarding their future operation. The Rialto Mining Corporation operated its No. 3 mine and mill continuously; the No. 2 mill, handling tailings since 1938, was remodeled early in 1942 to treat mine ore from the reopened No. 2 mine and was run as a mine mill until it burned on February 12, 1943. The corporation reopened its No. 4 mine (old L. & G.) about September 1942 and concentrated the ore in the No. 2 mill. Soon after this mill burned the No. 3 mill began operating three shifts daily and handled ore from other company mines in addition to that from the No. 3 mine.

The Jane E. Mining Co. reopened its Scott mill January 1, 1942, and resumed the milling of Scott mine ore; the crude ore mined from this property in 1941 was sent to the Central mill. Development work done at the Scott mine in 1942 included sinking a 275-foot shaft and 1,945 feet of churn drilling. Evans-Wallower Zinc, Inc., ran its No. 7 mine and mill continuously in 1942, and its No. 4 mine and mill from January 1 through February 26 when operations were suspended pending conversion of the No. 4 mill into a tailing plant to re-treat old tailings from the old Golden Rod property on which the company had Milling of the tailings and some mine ore was begun obtained a lease. in June and continued the rest of the year. The Weidman Mining Co. ran the Woodchuck and Townsite mines, treating the ore, as well as some custom ore, in the Woodchuck mill. The United Zinc Smelting Corporation continued to operate its Royal mine and mill; the mill also handled custom ore, mostly from the Dixie R. mine. The Mission mill of the Mission Mining & Royalty Co. treated both company and custom ore. Other mine mills operating steadily during the year were the Kansas Exploration (Ritz), Lawyers, Lula Bell (Farmington), and St. Louis No. 4. The Hudson Goodeagle, Roan Bull, Romo, and Smoky Hill mine mills were operated part of the year on a small scale. The M. & W. Mining Co. continued to work the Federal Brewster mine and reopened and operated the adjoining Huttig; the ore was shipped to custom mills. During the year the company obtained a lease on the Ninety-Six Brewster and sank a shaft into new ore bodies, which were brought into production early in 1943. Beck Mining Co. mill was run steadily in 1942 on company and custom ore from various mines in Oklahoma and Kansas. mills in Oklahoma that were active in 1941 and continued running in 1942 were the Atlas, Big Chief, Britt & Britt, Cardin Nos. 2 and 3, Semple (Martin), Tri-State Zinc (Ottawa and Sooner), and Western. Tri-State Zinc, Inc., experimented with the H. H. sink-and-float process in the treatment of Tri-State tailings in a commercial-size plant built during the year adjacent to the Sooner mill; the plant was shut down in the latter part of the year. The C. G. & C. Co. leased tailing piles on the Skelton property and acquired the old Skelton mine mill, which was converted into a tailing plant with a capacity of 75 tons an hour; the mill was placed in operation in June and ran the

rest of the year except for a temporary shut-down for repairs and improvements.

#### WISCONSIN

Government premium payments for over-quota production of lead and zinc resulted in a sizable increase in zinc production from old mines and dumps in the Wisconsin and Northern Illinois parts of the Upper Mississippi Valley region in 1942, but the mines in the Iowa part remained idle. The principal producer of finished (smeltinggrade) concentrates in the region continued to be the Vinegar Hill Zinc Co., which operated its custom mill near Cuba City on crude ore and zinc-iron-lead rougher jig concentrates purchased from operators throughout the active areas. Plant alterations and installation of additional equipment to increase the capacity of the mill were begun under a Defense Plant Corporation agreement late in 1942 and completed February 22, 1943. The enlarged mill has a capacity of 400 to 500 tons daily, and the equipment includes crushing and sampling units, rougher jigs, two separate ball-mill grinding and selective flotation units, tables, thickeners, and filters. The lead and zinc concentrates produced in 1942 were shipped to smelters outside the State, and the iron concentrates were used to make sulfuric acid in the company plant adjoining the mill. Besides the 79,539 tons of ore and bulk concentrates treated during the year, the company bought for the account of the Metals Reserve Co. about 22,000 tons of crude ore, which was stock-piled pending completion of the mill expansion The stock-piled ore is not included in the production for 1942 shown in the tables of this chapter but will be credited to that for the year (probably 1943) in which the ore is reduced to concentrates of smelting grade. This step is necessary before the quantity of metal actually recovered from the ore can be determined.

Shipments to the mill from Northern Illinois in 1942 (comprising the total output from that area) amounted to 22,402 tons of crude ore averaging 11.86 percent zinc and 0.53 percent lead, of which 16,537 tons were reduced to finished concentrates during the year and yielded 1,700 tons of recoverable zinc and 133 tons of lead. Shipments from Wisconsin included both crude ore and rougher jig concentrates. Shippers of jig-mill concentrates comprised the Big Jack Mining Co. (operating the Liberty mine), the C. F. & H. Mining Co. (Mulcahy mine), Coughlin Mining Co., Four S. & B. Mining Co., Little Benny Mining Co. (Monroe mine), and Wm. Blair Baggaley (Kittoe tailing dump). Principal shippers of Wisconsin crude ore, in order of rank, were the Cuba Mining Co., B. A. T. mine; Meloy & Baker, Martin mine; Gill Bros., James and Cleveland mines; R. J. Teske, McCabe mine; Depp Mining Co.; Mathey Mining Co., DeRocher mine; Francis B. Piquette, Trego mine; and Carter & Meloy, Leadmine mine.

The Dodgeville Mining Co. continuously operated its leased group of Dodgeville city lots and 150-ton jig- and flotation-concentration mill. Ore treated totaled 54,774 tons, yielding 2,451 tons of zinc concentrates averaging 61.20 percent zinc and 412 tons of lead concentrates averaging 74.02 percent lead. W. E. Faithorn erected a 600-ton tailing mill equipped with jigs and flotation machines on the Champion property at New Diggings; the mill was operated from July to December and produced 781 tons of 58.5-percent zinc concentrates.

At the Field property near Shullsburg the Chestnut Hill Zinc Co. did construction work on a flotation- and table-concentration mill, which was completed and put in operation on tailings in April 1943. During the latter part of 1942 Bureau of Mines engineers examined 45 zinc and lead mines on 14 separate properties in Wisconsin and approved an exploratory drilling project near Hazel Green, on which drilling began early in 1943.

Mine production of lead and zinc in Wisconsin, 1938-42

	Lead concentrates		Zinc co	ncentrates	Metal content 1				
Year			(sphalerite)		Lead		Zine		
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	
1938 1939 1940 1941 1942	493 567 621 1, 639 1, 092	\$21, 050 29, 327 34, 852 111, 014 104, 896	<sup>2</sup> 3, 895 <sup>3</sup> 10, 169 <sup>3</sup> 10, 875 <sup>3</sup> 11, 685 <sup>3</sup> 17, 449	2 \$121, 180 3 355, 915 3 447, 396 3 594, 323 4 1, 028, 828	320 388 445 1, 225 775	\$29, 440 36, 472 44, 500 139, 650 103, 850	2, 073 5, 904 5, 770 6, 238 9, 426	\$199, 008 614, 016 727, 020 935, 700 1, 753, 236	

<sup>1</sup> In calculating metal content of the ores from assays allowance has been made for roasting and smelting losses of both lead and zinc. In comparing the values of ores and metal it should be borne in mind that the value given for the ore is that actually received by the producer, whereas the value of the lead and zinc

the value given for the ore is that actually received by the producer, whereas the value of the lead and zinc is calculated from the average price for all grades.

? The zinc concentrates shipped in 1938 were a flotation product or raw concentrates roasted at Cuba City, Wis. No raw concentrates were shipped in 1938; about 13,000 tons were produced.

? Most of the ore mined in Wisconsin from 1939-12 was first treated in gravity-concentration mills producing bulk concentrates which were re-treated by flotation.

! The bulk of the finished zinc concentrates and part of the lead concentrates produced in Wisconsin in 1942 came from a custom mill treating purchased crude ores and low-grade bulk concentrates on which premium payments had been made previously to mine operators; therefore, the value of these concentrates is calculated at market prices. Premium payments not reflected in the value of the finished concentrates amounted to about \$399,000 for zinc and \$18,500 for lead; part of these payments, however, were for ore which was stock-piled and will not be treated until 1943.

Tenor of lead and zinc ore and old tailings milled and concentrates produced in Wisconsin, 1941-42

	19	041	19	142
	Crude ore	Old tailings	Crude ore	Old tailings
Total ore, etc., milledshort tons_ Total concentrates produced: 1	211, 973		208, 032	93, 642
Leaddododo	1, 639 11, 685		1, 092 16, 543	906
Ratio of concentrates to ore, etc.: 2 Leadpercent	0. 77		0. 52	
Zincdod Metal content of ore, etc.: 3	5. 51		7.95	0.97
Leaddodo	. 59 3. 27		. 39 4. 78 74. 27	. 57
Average lead content of galena concentratesdo Average zinc content of sphalerite concentratesdo	76. 27 59. 77		60. 12	58. 83
Average value per ton: 4 Galena concentrates	\$67. 73 51. 39		\$96.06 58.07	\$75. 22

Most of the ore mined in Wisconsin in 1941-42 was first treated in gravity-concentration mills producing

Nost of the ore filling in Wisconsin in 1942 was hist treated in gravity-concentrates which were re-treated by flotation.

Percentage represent sents finished flotation concentrates.

Percentages represent metal content of the ore insofar as it is recovered in the concentrates.

The bulk of the finished zinc concentrates and part of the lead concentrates produced in Wisconsin in 1942 came from a custom mill treating purchased crude ores and low-grade bulk concentrates on which premium payments had been made previously to mine operators; therefore, the value of these concentrates is calculated at market prices.

# GOLD, SILVER, COPPER, LEAD, AND ZINC IN COLORADO

(MINE REPORT)

#### By Chas. W. HENDERSON

#### SUMMARY OUTLINE

		Page		Page
Summary		317	Metallurgic industry	323
Calculation of val	ue of metal production	318	Review by counties and districts	327
	counties		Golden Cycle mill	332
Mining industry		321	Leadville district	334
Ore classification		322	Cripple Creek district	342

#### SUMMARY

Colorado mines yielded gold, silver, copper, lead, and zinc valued, in terms of recovered metals, at \$19,896,623 in 1942 compared with \$23,877,597 in 1941. (See fig. 1.) Gold and silver together represented 58 percent of the total value in 1942 and 77 percent in 1941. Gold production decreased 29 percent in 1942 from 1941. The quantity of silver and copper produced decreased 58 and 84 percent, respectively, lead increased 21 percent, and zinc 105 percent. The number of producing lode mines decreased from 579 in 1941 to 311 in

1942; the number of placer mines decreased from 324 to 68.

The Government, through its agency the Metals Reserve Company, announced that effective February 1, 1942, premiums of 5 cents per pound for copper and 2% cents per pound for both lead and zinc would be paid for these metals produced in excess of fixed basic quotas. The ceiling prices for these metals at that date and as of July 1943 were: Copper, electrolytic, 11.775 cents per pound f. o. b. Atlantic seaboard refineries; lead 6.50 cents (New York); and zinc 8.25 cents (St. Louis). The quota for each mine or mining company was based on 1941 production. On December 1, 1942, arrangements for additional premium payments for overquota metal production were announced by the Metals Reserve Company. Operators who could argue their inability to maintain present rate of production without loss of money or who could assure additional output were eligible for these additional Government subsidies for copper, in several steps of 5 cents a pound for each step; for lead and zinc, steps of 2% cents a pound.

All tonnage figures are short tons and "dry weight"; that is, they do

not include moisture.

The value of metal production herein reported has been calculated at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

	Yes	ur	Gold 1	Silver 2	Copper 3	Lead 4	Zine 4
1938			Per fine ounce \$35.00	Per fine ounce 5 \$0.646+		Per pound \$0.046	Per pound \$0,048
1939 1940 1941			35. 00 35. 00 35. 00	6.678+ 7.711+ 7.711+	. 104 . 113 . 118		. 052 . 063 . 075

<sup>1</sup> Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934. was \$20.67+(\$20.671835) per fine ounce.

<sup>2</sup> Treasury buying price for newly mined silver.

<sup>3</sup> 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Company for over-quota production but excludes value of foreign copper delivered to Metals Reserve Company for domestic consumption.

<sup>4</sup> 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Company for over-quota production.

<sup>5</sup> \$0.64646464.

Annual figures for the 5 years ended with 1942 and total production from 1858 are given in the table that follows. To the end of 1941 Colorado had produced more silver than any other State, but the decreased output in 1942 allowed Montana to pass it.

Mine production of gold, silver, copper, lead, and zinc in Colorado, 1938-42, and total, 1858-1942, in terms of recovered metals

Year	Mines pro- ducing		Ore sold or treated	Gold (lode	and placer)	Silver (lode and placer)		
	Lode	Placer	(short tons)	Fine ounces	Value	Fine ounces	Value	
1938 1939 1940 1941 1942	669 758 691 579 311	592 583 439 324 68	1, 996, 095 1, 914, 593 2, 157, 765 2, 222, 786 1, 797, 386	367, 468 366, 852 367, 336 380, 029 268, 627	\$12, 861, 380 12, 839, 820 12, 856, 760 13, 301, 015 9, 401, 945	7, 932, 095 8, 496, 488 9, 710, 709 7, 301, 697 3, 096, 211	\$5, 127, 819 5, 767, 313 6, 905, 393 5, 192, 318 2, 201, 750	
1858-1942			(1)	38, 565, 382	843, 665, 334	721, 046, 775	560, 682, 926	

Year	Cop	oper	L	ead	Zi	Total value	
1 ear	Pounds	Value	Pounds	Value	Pounds	Value	1 otal value
1938	28, 342, 000 26, 430, 000 24, 304, 000 13, 496, 000 2, 204, 000	\$2,777,516 2,748,720 2,746,352 1,592,528 266,684	18, 910, 000 16, 444, 000 22, 952, 000 25, 148, 000 30, 362, 000	\$869, 860 772, 868 1, 147, 600 1, 433, 436 2, 034, 254	9, 106, 000 3, 660, 000 10, 120, 000 31, 444, 000 64, 430, 000	\$437, 088 190, 320 637, 560 2, 358, 300 5, 991, 990	\$22, 073, 663 22, 319, 041 24, 293, 665 23, 877, 597 19, 896, 623
1858-1942	² 245, 396	64, 765, 883	2 2, 392, 072	226, 729, 967	<sup>2</sup> 1, 183, 229	167, 578, 686	1, 863, 422, 796

<sup>1</sup> Figures not available.

2 Short tons.

Gold and silver produced at placer mines in Colorado, 1938-42, in fine ounces, in terms of recovered metals

	Sluicing and											
Year		ng and caulic	Drift n	nining	Dry-	land 1	Drag float		Floa		Tot	al
	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver
1938 1939 1940 1941 1942	2, 285 2, 535 1, 822 1, 886 1, 802	433 498 360 402 335	1, 362 15	279 1	10, 201 10, 631 10, 203 13, 052 119	2, 020 2, 436 2, 210 2, 580 9	3, 166 1, 950 4, 817 6, 173	279 178 553 945	1,027 4,688 4,975 10,622 14,523	239 1, 012 1, 068 2, 152 2, 913	18, 041 19, 819 17, 000 30, 377 22, 617	3, 250 4, 125 3, 638 5, 687 4, 202

Dragline and power-shovel excavators with sluices or special amalgamators.

Gold.—The output of recoverable gold from lode mines in Colorado decreased from 349,652 fine ounces in 1941 to 246,010 fine ounces in 1942; the production of gold from placer mines decreased 7,760 fine ounces.

Silver.—Mine production of recoverable silver in Colorado was 3,096,211 fine ounces in 1942, compared with 7,301,697 fine ounces in 1941. Dry and siliceous ores yielded 69 percent of the total silver; zinc and zinc-lead ores, 29 percent; and other types of ores, with a very small quantity of silver from placer mines, 2 percent.

Copper.—The output of recoverable copper from mines in Colorado in 1942 was 2,204,000 pounds compared with 13,496,000 pounds in




FIGURE 1.—Value of mine production of gold, silver, copper, lead, and zinc in Colorado, 1870-1942. The value of copper has been less than \$2,000,000 annually, except in a few years.

1941. Eagle County produced 29 percent of the State total in 1942

compared with 83 percent in 1941.

Lead.—The mine production of recoverable lead in Colorado was 30,362,000 pounds in 1942 compared with 25,148,000 pounds in 1941. Zinc-lead ore yielded 67 percent of the total lead; dry and siliceous ores 28 percent; and lead, copper, zinc, and lead-copper ores together,

5 percent.

Zinc.—The output of recoverable zinc from mines in Colorado increased 105 percent in quantity in 1942 over 1941. Largely responsible for this increase was the New Jersey Zinc Co. Empire Zinc Division Eagle mine at Gilman, Eagle County, which resumed mining and milling zinc-lead ore in June 1941 and continued throughout 1942. Other principal zinc-producing districts in 1942 were: California (Leadville), Lake County; Pioneer (Rico), Dolores County; Ten Mile, Summit County; and Buckskin, Park County.

## MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in Colorado in 1942, by counties, in terms of recovered metals

		Mines p	roducing	Gold (lode	and placer)	Silver (lode	and placer)
County		Lode	Placer	Fine ounces	Value	Fine ounces	Value
Adams		43 3 45	1 4 2	274 15, 920 268 18, 105	\$9, 590 557, 200 9, 380 633, 675 245	45 26, 900 1, 274 207, 139	\$32 19, 129 906 147, 299
Custer Dolores Eagle Fremont		$\begin{array}{c}4\\2\\2\\1\end{array}$		119 2, 040	4, 165 71, 400	384 110, 918 395, 252 66	273 78, 875 281, 068 47
GarfieldGilpin		$\begin{array}{c}1\\24\\2\end{array}$	13	5, 390	188,650	56 15, 179 540	40 10, 794 384
Gilpin Grand Gunnison Hinsdale Jefferson Lake La Plata Larimer		29 3	7 3	1, 322 26 432 27, 235 390 8	46, 270 910 15, 120 953, 225 13, 650 280	9, 132 6, 798 73 243, 474 377	6, 494 4, 834 52 173, 137 268 2
Mesa Mineral Montezuma Montrose Ouray Park Pitkin Rio Grande Morande Montrose Montro		2 6 2 1 19 10 5	5 	644 218 15 6, 782 37, 370 1 5, 499	22, 540 7, 630 525 237, 370 1, 307, 950 35 192, 465	59 805, 202 741 2, 762 141, 411 26, 830 286, 131 7, 186	42 572, 588 527 1, 964 100, 559 19, 079 203, 471 5, 110
Routt- Saguache San Juan San Miguel Summit Teller		1 9 16 9 17 42	1 11	60 17, 094 23, 451 1, 502 104, 455	2, 100 598, 290 820, 785 52, 570 3, 655, 925	28 41, 313 394, 657 315, 820 40, 801 15, 660	20 29, 378 280, 645 224, 583 29, 014 11, 136
Total, 1941		311 579	68 324	268, 627 380, 029	9, 401, 945 13, 301, 015	3, 096, 211 7, 301, 697	2, 201, 750 5, 192, 318
County	Сорј	per	L	ead	Zi	ne	Total
County	Pounds	Value	Pounds	Value	Pounds	Value	value
Adams_Boulder_Chaffee_Clear Creek_Costilla_	39, 900 800 72, 300	\$4,828 97 8,748	147, 700 12, 000 1, 023, 700	0 68,588	8,200	\$530 763 42, 966	\$9, 622 591, 583 11, 950 901, 276 245
Custer Dolores Eagle Fremont Garfield Gilpin	70, 100 645, 700 600 122, 300	8,482 78,130 73	7,000 4,564,100 4,480,700 400 112,300	0 300, 207	5, 528, 800 45, 760, 400 14, 300 2, 900	514, 178 4, 255, 717 1, 330 270	742 911, 495 4, 986, 522 1, 450 337 221, 766
Grand Gunnison Hinsdale Jefferson	3,600 6,000	436 726	1, 000 186, 200 295, 600	67 12,475 19,805	117, 300		451 76, 584 26, 275 15, 172
Lake La Plata	130, 300	15, 766	6, 703, 700	449, 148	6,688,000	621, 984	2, 213, 260 13, 918
Larimer Mesa Mineral Montezuma	2, 100 77, 600	254 9,390	1,051,600	70,457			282 296 674, 975 8, 157
Montrose Ouray Park Pitkin Rio Grande	16, 600 141, 300 78, 400 1, 000 93, 400	2,009 17,097 9,486 121 11,301	799, 300 543, 600 629, 800 800	J   04	912,000 284,000	26, 412	4, 498 474, 479 1, 457, 752 272, 236 208, 930
Routt	36, 400 575, 000 78, 800 11, 800	4, 404 69, 575 9, 535 1, 428	878, 900 4, 297, 000 3, 436, 700 1, 189, 200	58,886 0 287,899 0 230,259	784,000 780,000	446 61,715 72,912 72,540 158,602	513 156, 483 1, 309, 321 1, 357, 702 321, 290 3, 667, 061
Total, 1941.	2, 204, 000 13, 496, 000	266, 684 1, 592, 528	30, 362, 000 25, 148, 000	2, 034, 254 0 1, 433, 436	64, 430, 000	5, 991, 990 2, 358, 300	19, 896, 623 23, 877, 597

Ore sold or treated and gold and silver produced at lode mines in Colorado in 1942, by counties, in terms of recovered metals

County	Ore sold or treated (short tons)	Gold (fine ounces)	Silver (fine ounces)
Boulder	37, 207	15,920	26,900
Chaffee		73	1, 246
Clear CreekCuster		18, 105	207, 139 384
Dolores		119	110.918
Eagle	-10' -00	2,040	395, 252
Fremont		2,010	66
Garfield	10		50
Gilpin	16, 135	5, 120	15, 12
Grand			540
Gunnison	7,622	1,322	9, 132
Hinsdale	3,685	26	6, 798
Lake	365, 033	27, 204	243, 464
Lake La Plata	66	390	377
Larimer	7	8	
Mesa			59
Mineral	39, 243	644	805, 20
Montezuma	1,619	218	741
Montrose	138	0 700	2,759
Ouray	38,605	6,782	141, 411
Park		17, 189	23, 15
Pitkin		F 405	286, 13
Rio Grande		5, 497	7, 180 20
Routt			41, 31
Saguache		17, 093	394, 657
San Juan	197, 404		315, 82
San Miguel Summit	179,003	23, 451	40, 486
summit	10, 289	104, 455	15, 660
Гeller	377, 995	104,455	10,000
	1,797,386	246, 010	3, 092, 009
Гotal, 1941	2, 222, 786	349,652	7, 296, 010

Gold and silver produced at placer mines in Colorado in 1942, by counties, in fine ounces, in terms of recovered metals

			Dredges							
County	Sluicing and hydraulic		Dry-land 1		Dragline floating		Floating bucket		Total	
	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver
Adams Chaffee Costilla Gilpin Jefferson Lake Montrose Park	274 195 7 270 432 31 14 484	45 28 52 73 10 3 99	119	9	6,173	945	13, 405	2, 623	274 195 7 270 432 31 14 20,181	45 28 52 73 10 3,676
Rio Grande San Juan Summit	2 1 92	25					1,118	290	1, 210	315
Total, 1941	1,802 1,886	335 402	119 13, 052	2, 580	6, 173 4, 817	945 553	14, 523 10, 622	2, 913 2, 152	22, 617 30, 377	4, 202 5, 687

<sup>&</sup>lt;sup>1</sup>Dragline and power-shovel excavators with sluices or special amalgamators.

#### MINING INDUSTRY

The variation and complexity of Colorado ores allowed mines to meet the shifting and complexing Government orders, as well as changes in the prices for metal. Except for the Cripple Creek district, virtually all the ores in Colorado districts—although chiefly valuable for gold and silver—contain some zinc, often discarded. A change in selection of ore and in metallurgy converted many mines

into producers of zinc concentrates or products containing recoverable zinc. This change is shown clearly by a comparison of the county and district tables for 1939 and 1942.

Effective March 2, 1942, the War Production Board issued an amendment to Order P-56, placing the mining industry on a par with manufacturers of war materials. Among other instructions, this amendment provided that mines at which the value of gold, silver, or both produced exceeded 30 percent of the value of the total metal output would no longer be entitled to priority ratings assigned under Order P-56. This amendment deprived virtually all gold mines in Colorado of essential equipment and supplies and forced many operators to close long before the Gold Mining Limitation Order of October 8, 1942. Later, upon appeal, this amendment to Order P-56 was voided.

Dredging operations ceased immediately upon the date set for closing by Order L-208—called the Gold Mining Limitation Order (see Gold and Silver chapter for text of order). Cripple Creek lode district, upon appeal, was given a reprieve until June 8, 1943, but the exodus of miners that had begun in March greatly increased. Splitcheck lessees, indigenous to that district (and the producers of 80 percent of the ore), who had generally kept at work, began drifting away after the issuance of Order L-208 and continued to do so in 1943, with the result that several of the largest mines ceased operations in March.

#### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

Ore sold or treated in Colorado in 1942, with content in terms of recovered metals

Source	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)
Dry and siliceous gold ore Dry and siliceous gold-silver ore Dry and siliceous silver ore	932, 145 192, 709 88, 132	188, 682 25, 077 2, 407	293, 231 399, 586 1, 428, 333	597, 574 122, 738 716, 619	2, 138, 734 4, 012, 497 2, 477, 385	735, 874 780, 000 284, 000
	1, 212, 986	216, 166	2, 121, 150	1, 436, 931	8, 628, 616	1, 799, 874
Copper ore Lead ore Lead-copper ore Zinc ore Zinc-lead ore	208 6, 418 22 590 577, 162	1, 451 24 6 28, 319	3, 189 61, 717 493 2, 514 902, 946	26, 286 26, 513 2, 192 2, 200 709, 878	865 1, 442, 554 3, 483 40, 822 20, 245, 660	429, 899 62, 200, 227
	584, 400	29, 844	970, 859	767, 069	21, 733, 384	62, 630, 126
Total, lode mines Total, placers	1, 797, 386	246, 010 22, 617	3, 092, 009 4, 202	2, 204, 000	30, 362, 000	64, 430, 000
Total, 1941	1, 797, 386 2, 222, 786	268, 627 380, 029	3, 096, 211 7, 301, 697	2, 204, 000 13, 496, 000	30, 362, 000 25, 148, 000	64, 430, 000 31, 444, 000

#### METALLURGIC INDUSTRY

The total ore sold or treated in Colorado was 1,797,386 tons in 1942 compared with 2,222,786 tons in 1941. The quantity of zinclead ores sold or treated increased from 434,200 tons in 1941 to 577,162 tons in 1942, most of the increase coming from Eagle County; dry and siliceous ores decreased from 1,572,763 tons to 1,212,986; copper ore decreased from 207,678 tons to 208, owing almost entirely to conversion to zinc-lead mining and milling at the New Jersey Zinc Co. Empire Zinc Division Eagle mine at Gilman, Eagle County; lead ore decreased from 7,917 tons to 6,418; and zinc ore increased from 224 tons to 590.

Direct smelting ore comprised 3 percent of the State total output of ore in 1942 as compared with 11 percent in 1941. The Arkansas Valley lead bullion-leady copper matte smelter at Leadville purchased most of the gold, silver, and gold-silver-lead-copper ores and

concentrates shipped to smelters during the year.

Ore and concentrates were shipped to smelters in other States as follows: Zinc-lead sulfide ores and concentrates from Lake and Saguache Counties to Coffeyville, Kans.; zinc concentrates from Clear Creek, Dolores, Ouray, Park, Pitkin, San Juan, San Miguel, and Summit Counties to Amarillo, Tex.; and silver-gold-copper-lead ore from Eagle County, gold-silver-copper ores and concentrates from Gilpin, Mesa, Montrose, Ouray, Rio Grande, and San Juan Counties, and zinc-lead-copper-silver-gold ores and concentrates from Garfield, Lake, Ouray, Saguache, and San Juan Counties to Utah smelters.

The quantity of gravel handled in 1942 by two floating connected-bucket dredges, one dragline floating dredge, and one dry-land dredge was approximately 2,919,406 cubic yards. Specific data on yardage handled at small-scale placer operations are not obtainable because the operators do not know the quantity of gravel sluiced.

Mine production of metals in Colorado in 1942, by methods of recovery, in terms of recovered metals

		ye steeds				
	Material treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Ore and concentrates gamated 1 Ore, old tailings, concentrates	717, 716	60, 233	15, 906			<u> </u>
sands, and slimes cyar Concentrates smelted Ore smelted Placer 1	1ided ½ 3 272, 889 140, 590 48, 173	86, 132 91, 219 8, 426 22, 617	13, 202 2, 446, 104 616, 797 4, 202	1, 467, 753 736, 247	27, 800, 925 2, 561, 075	63, 874, 212 555, 788
Total, 1941		268, 627 380, 029	3, 096, 211 7, 301, 697	2, 204, 000 13, 496, 000	30, 362, 000 25, 148, 000	64, 430, 000 31, 444, 000

<sup>1</sup> Quicksilver used by amalgamation mills was 3,429 pounds. Placer mines used approximately 115 pounds.

 <sup>2</sup> Cyanide (in terms of 96- to 98-percent NaCN) used was 529,747 pounds.
 3 Comprises 253,551 tons of sands and slimes from ore and iron concentrates first roasted and amalgamated and 19,338 tons of combined flotation concentrates and crude ore cyanided direct.

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in Colorado in 1942, by counties, in terms of recovered metals

			ered in lion	•	Concentrates smelted and recovered metal						
County	Ore treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Con- cen- trates pro- duced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)		
Boulder	30, 576 10	9,997	1,892	1,736	3, 043	8, 595	13, 281	113, 477			
Clear Creek Eagle	68, 378	10, 204	1, 221 45	2, 424	3, 725	17,976	17,677	224, 226			
Gilpin Gunnison	3, 587 6, 270	240 584	55	322	763	3,661	14,766	19,859			
Lake Larimer	259, 162 7	9, 423 8	366 3, 203 3	7,948	191 6, 105	2, 141 80, 201	124, 973	7, 696 729, 528	196, 174		
Montezuma	1,600	134	49	16	42	672					
Ouray Park	33, 562	4, 518 39	1,370	2, 449	2,039	105, 826	130, 400	618, 134	539, 700		
Rio Grande	14,970	1,969	1,548	975	3,528	5, 638	93, 400	800			
San Miguel Teller	146, 301 362, 486	6, 465 102, 757	4, 815 14, 528	14, 556	14,368	199, 530		2, 399, 166	780,000		
Total, 1941	926, 909 1, 244, 184	146, 365 203, 191	29, 108 53, 614	30, 520 33, 027	33, 804 48, 450	424, 240 596, 758	394, 497 469, 407	4, 112, 886 3, 483, 823	1, 515, 874		

<sup>1</sup> Less than 1/2 ton.

Zinc.

Zinc-lead....

34

574, 664

822, 304

10

28, 306

57, 415

891, 123

2,021,864

92, 447

110,070

#### Mine production of metals from concentrating mills in Colorado in 1942, in terms of recovered metals

14, 300 62, 060, 038

62, 358, 338

600

19, 826, 593

23, 688, 039

704, 581

1,073,256

#### BY COUNTIES Concentrates smelted and recovered metal Ore treated Concen-(short Gold trates Silver (fine Copper Lead Zinc tons) produced (fine ounces) (pounds) (pounds) (pounds) (short ounces) tons) 14, 897 343 177, 796 110, 918 142, 786 5,890 Boulder. 32, 885 5, 109 761, 449 4, 564, 100 4, 342, 087 5, 700 8, 200 462, 000 528, 800 1,642 18 7, 585 387 Chaffee Clear Creek Dolores 17 45, 544 35, 371 227, 248 4, 108 119 363 3, 743 9, 824 52, 069 70, 100 Eagle.. 57, 257 10 45, 760, 400 14, 300 20, 534 Fremont. 34 95, 130 3, 400 5, 800 66 66 9, 905 3, 737 6, 608 109, 260 595, 798 26, 775 18, 063 252, 295 34 12, 324 1, 136 3, 680 92, 718 34, 119 4, 904 92, 104 9, 000 19 81, 156 114, 069 295, 600 4, 697, 856 856, 335 162, 369 497, 418 488, 155 700 465, 854 4, 277, 864 2, 014 271 274 Gilpin\_\_\_\_ Gunnison\_\_\_ 2, 715 265 117, 300 Hinsdale.... 26 12, 279 2, 361 1, 704 74, 041 9, 793 58, 803 9, 967 6, 395, 419 Mineral. 576 168, 900 912, 000 284, 000 4, 800 531, 499 781, 620 Ouray..... 536 Park... 5, 723 15, 831 819 Pitkin... 252, 295 1,000 Routt\_ 28 1,030 7,110 3,307 2,500 702 3, 320 197, 063 32, 683 9, 598 12, 208 571, 835 78, 800 9, 467 Saguache\_\_\_\_ 17, 930 392, 277 110, 558 26 San Juan 17,038 2,613 217 4, 277, 864 1, 033, 634 San Miguel Summit.... 30, 692 1, 132 1,011,399 1,383,400 Teller.... 15, 509 1,698 822, 304 730, 982 110, 070 73, 097 57, 415 62, 748 2, 021, 864 1, 807, 373 1,073,256 1,641,587 23, 688, 039 16, 716, 067 62, 358, 338 31, 404, 929 Total, 1941.... BY CLASSES OF ORE TREATED Dry and siliceous gold-Dry and siliceous gold-silver\_\_\_\_\_ 147, 538 9, 157 24,534 37, 341 163,869 464,888 42, 898 56, 260 4.313 3, 871 663 179,875 117, 302 1, 370, 014 910, 318 3, 141 Dry and siliceous silver. 4,004 86, 154 750 941, 127 85, 417 284,000 Lead 910 139 41

Gross metal content of concentrates produced from ores mined in Colorado in 1942, by classes of concentrates smelted

	Concen-	Gross metal content								
Class of concentrates	trates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (wet assay) (pounds)	Lead (wet assay) (pounds)	Zine (pounds)				
Dry gold	11, 387 197 1, 856 47, 403 3, 175	18, 452 128 3, 015 58, 248 8, 001	79, 656 5, 023 8, 424 1, 918, 157 229, 152	259, 216 4, 783 129, 532 502, 753 586, 691	607, 019 56, 872 9, 706 26, 796, 399 1, 742, 692	111, 319 1, 608 13, 835 4, 045, 318 385, 519				
Total to copper and lead plants	64, 018	87, 844	2, 240, 412	1, 482, 975	29, 212, 688	4, 557, 599				
ZincZinc-lead	73, 180 3, 392	1, 515 2, 341	123, 823 122, 408	133, 993 189, 592	1, 065, 515 742, 740	70, 901, 370 1, 191, 376				
Total to zinc plants	76, 572	3, 856	246, 231	323, 585	1, 808, 255	72, 092, 746				
Total, 1941	140, 590 106, 124	91, 700 111, 321	2, 486, 643 2, 425, 238	1, 806, 560 2, 580, 943	31, 020, 943 22, 542, 261	76, 650, 345 41, 495, 808				

Mine production of metals from Colorado concentrates shipped to smelters in 1942, in terms of recovered metals

#### BY COUNTIES

	Concentrates (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Boulder	2, 024	4, 685	23, 492	20, 866	146, 362	5, 700
	17	18	343	387	5, 109	8, 200
Chaffee Clear Creek	6, 167	7,833	195, 772	69, 746	985, 675	462,000
Dolores	9,824	119	110, 918	70, 100	4, 564, 100	5, 528, 800
Eagle	57, 257	363	142, 786	20, 534	4, 342, 087	45, 760, 400
Fremont	10		66	600		14, 300
Gilpin	2, 336	3, 478	13, 566	109, 896	101, 015	
GilpinGunnison	365	456	5, 878	3, 400	121, 765	117, 300
Hinsdale	274	26	6,608	5, 800	295, 600	
Lake		16,072	189, 461	126, 677	5, 427, 384	6, 591, 593
Mineral		576	595, 798	74, 041	856, 335	
Montezuma		42	672			
		2, 232	132, 601	140, 193	780, 503	708, 600
Ouray Park	5, 723	15, 831	18, 063	58, 803	497, 418	912,000
Pitkin	819	,	252, 295	1,000	488, 155	284,000
Rio Grande		3, 528	5, 638	93, 400	800	l
Routt	5	0,020	28	1	700	4,800
Saguache		26	17, 930	12, 208	465, 854	531, 499
San Juan		17,038	392, 277	571, 835	4, 277, 864	781, 620
San Miguel		16, 981	310, 088	78, 800	3, 432, 800	780, 000
Summit	2, 500	217	30, 692	9, 467	1, 011, 399	1, 383, 400
Teller	702	1,698	1, 132			
	140, 590	91, 219	2, 446, 104	1, 467, 753	27, 800, 925	63, 874, 212
Total, 1941	106, 124	111, 198	2, 404, 131	2, 110, 994	20, 199, 890	31, 404, 929

#### BY CLASSES OF CONCENTRATES SMELTED

Dry gold	11, 387 197 1, 856 47, 403 3, 175	18, 452 128 3, 015 58, 248 8, 001	79, 656 5, 023 8, 424 1, 918, 147 229, 152	222, 080 3, 827 103, 626 398, 877 469, 317	546, 068 51, 185 8, 736 24, 220, 390 1, 568, 422	
Total to copper and lead plants	64, 018	87, 844	2, 240, 402	1, 197, 727	26, 394, 801	
Zinc-lead	73, 180 3, 392	1, 034 2, 341	83, 294 122, 408	108, 914 161, 112	693, 048 713, 076	63, 123, 495 750, 717
Total to zinc plants	76, 572	3, 375	205, 702	270, 026	1, 406, 124	63, 874, 212
	140, 590	91, 219	2, 446, 104	1, 467, 753	27, 800, 925	63, 874, 212

Gross metal content of Colorado crude ore shipped to smelters in 1942, by classes of ore

			Gross metal content							
Class of ore	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)				
Dry and siliceous gold Dry and siliceous gold-silver Dry and siliceous silver Copper Lead Lead-copper	5, 235 2, 274 31, 872 208 5, 508 22	4, 776 409 1, 744 44 1, 410 24	11, 368 10, 885 518, 015 3, 189 58, 576 493	51, 614 4, 357 689, 406 28, 567 33, 108 2, 742	10, 869 215, 494 631, 836 961 1, 502, 245 3, 916	1, 357 245, 790 74, 109				
Total to copper and lead plants	45, 119	8, 407	602, 526	809, 794	2, 364, 821	321, 256				
Zinc-lead	556 2, 498	6 13	2, 715 11, 823	1, 833 6, 529	55, 863 462, 993	476, 005 199, 045				
Total to zinc plants	3, 054	19	14, 538	8, 362	518, 856	675, 050				
Total, 1941	48, 173 247, 620	8, 426 35, 263	617, 064 4, 838, 265	818, 156 11, 705, 347	2, 883, 677 6, 424, 479	996, 306 4, 270, 163				

Mine production of metals from Colorado crude ore shipped to smelters in 1942, in terms of recovered metals

#### BY COUNTIES

		00111111				
	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Boulder Chaffee Clear Creek	741 93 218	1, 238 39 68	1, 516 898 10, 146	19, 034 413 2, 554	1, 338 6, 891 38, 025	
Custer Eagle Garfield	24 16, 441 10	1,666	384 252, 421 56	625, 166	7, 000 138, 613 400	2,900
Gilpin Grand Gunnison	224 4 216	1, 402 282	1,506 540 2,888	12, 404	11, 285 1, 000 64, 435	
Hinsdale Lake La Plata Mesa	13, 153 66	1,709 390	50, 800 377	200 3, 623	1, 276, 316	96, 407
Mess Mineral Montezuma Montrose Montrose	5, 124 19	68 42	209, 404 20	2, 100 3, 559	195, 265	
Ouray Park Pitkin	138 139 1, 180 7, 842	1,319 1,319	2, 759 7, 440 5, 083 33, 836	16,600 1,107 19,597	18, 797 46, 182 141, 645	
San Juan San Miguel	1, 474 341 19	34 55 5	23, 383 2, 380 917	24, 192 3, 165	413, 046 19, 136 3, 900	132, 101 2, 380
summit	691 48, 173	75 8, 426	9, 794	2, 333	177, 801 2, 561, 075	322, 000 555, 788
Total, 1941	247, 620	35, 263	4, 838, 265	11,385,006	4, 948, 110	39, 071
· I	BY CLAS	SES OF C	ORE	T	1	1
Dry and siliceous gold Dry and siliceous gold-silver Dry and siliceous silver Copper Lead	5, 235 2, 274 31, 872 208 5, 508	4,776 409 1,744 44 1,410	11, 368 10, 885 518, 015 3, 189 58, 576	41, 476 3, 168 630, 465 26, 286 25, 763	9, 576 193, 867 536, 258 865 1, 357, 137	
Lead-copper		24	493	2, 192	3, 483	
Total to copper and lead plants  Zine	45, 119 556	8, 407	602, 526 2, 448	729, 350 1, 600	2, 101, 186	415, 599
Zinc-lead	2,498	13	11, 823	5, 297	419, 067	140, 189
Total to zinc plants	3, 054 48, 173	19 8, 426	14, 271 616, 797	6, 897 736, 247	459, 889 2, 561, 075	555, 788
	20, 170	0, 420	010, 797	100, 241	4, 501, 075	555, 788

### REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, lead, and zinc in Colorado in 1942, by counties and districts, in terms of recovered metals

County and district		produc- ng	Ore sold or treated	Gold	(fine ou	nces)	Silve	r (fine ou	nces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)	Total value
	Lode	Placer	(short tons)	Lode	Placer	Total	Lode	Placer	Total	(pounds)	(pounds)	(pounds)	value
Adams County		1			274	274		45	45				\$9,622
Boulder County:			1.5										
Central	6		2, 918	1,606		1,606	360		360	400	4, 100		- 56, 789
Gold Hill	15		24,020	8, 156		8, 156	9, 461		9, 461	10,600	118, 300	5, 700	301, 927
Grand Island	4		4, 474	1, 227		1, 227	13, 836	1	13, 836	2, 100	19,700		54, 358
Magnolia	4		444	612		612	3_		3				21, 422
Sugar Loaf	11		3, 280	2,644		2,644	1, 253	1	1, 253				93, 498
Ward	3		2,071	1,675		1,675	1, 987		1, 987	26,800	4,600		63, 589
Chaffee County:				1 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7 7			-,		•				
Chalk Creek	1	l	50	39		39	415		415	600	7,400	8, 200	2, 99
Granite		4	11	21	195	216	. 7	28	35				7.58
Monarch			82	13		13	824		824	200	4,600		1, 37
Hear Creek County					~								
Alice	2		1, 129	400		400	699		699	800	16,000		15, 66
Argentine	1		506				14, 732		14, 732		12,700		11, 32
Empire	4		29, 986	7,893		7,893	724		724	4,700	2,300		277, 49
Griffith *	4		9,700	51		51	133, 314		133, 314	5, 100	417, 000	462,000	168, 10
Idaho Springs 1	24		39, 504	6, 171		6, 171	30, 611		30, 611	56, 100	193, 300		257, 49
Montana	4		6, 161	53		53	22, 164		22, 164	3, 300	247, 100		34, 57
Trail Creek	6		27, 154	3, 537		3, 537	4 895		4,895	2, 300	135, 300		136, 61
Costilla County		2	,	.,	7	7	-,		-, -, -	-,			24
Custer County:		_			1								
Hardscrabble	3	I	18	1	1		384		384	~	4,000		54
Ilse			6				. 001		001		3,000		20
Onlores County: Pioneer (Rico)	2		35, 371	119		119	110, 918		110, 918	70, 100	4, 564, 100	5, 528, 800	911. 49
Oolores County: Pioneer (Rico) Eagle County: Red Cliff	2		243, 689				395, 252		395, 252	645, 700	4, 480, 700	45, 760, 400	4, 986, 52
remont County.			34	2,010	1	2,010	66		66	600	1, 100, 100	14, 300	1, 45
arfield County: Rifle Creek	î		10				56		56		400	2, 900	33
			1				50		, 00		100	2, 000	90
Southern Southern	21	13	15, 281	4,968	270	5, 238	14, 546	52	14, 598	115, 900	112, 300		215, 25
Northern	3	10	854	152	2.0	152	581	02	581	6,400	112,000		6, 50
rand County			4	102		102	540		540	0, 100	1 000		48
lunnian Country			- 2				- 010		040		1,000		-
Gold Brick	1 4		7, 109	1,317		1.317	3, 492		3, 492	600	19, 700		49, 97
Taylor Park	2		133	1, 517		1,016	3, 774		3, 774	2,000	66, 300	8, 400	8, 21
Tomichi			380	3		3	1,866		1, 866	1,000	100, 200	108, 900	18, 39
Insdale County:			300	. ?	1		1,800		1,800	1,000	100, 200	108, 900	18, 38
GalenaGale County:	2	1	2 000	26	1	26	6, 608	1	6, 608	5, 800	905 900	1	00.11
			3, 680	20		20_							26, 11
Lake	1		1 5				190		190	200			15
enerson county		. 7	I		432	432	'	. 73	73	1	1	·	15, 1

See footnote at end of table.

Mine production of gold, silver, copper, lead, and zinc in Colorado in 1942, by counties and districts, in terms of recovered metals—Continued.

County and district	Mines i	produc- ig	Ore sold or treated	Gold	l (fine ou	nces)	Silve	er (fine ou	ınces)	Copper	Lead	Zinc	Total
	Lode	Placer	(short tons)	Lode	Placer	Total	Lode	Placer	Total	(pounds)	(pounds)	(pounds)	value
Lake County: California (Leadville)	25	1	364, 641	27, 114	1	27, 115	241, 301		241, 301	130, 300	6, 696, 400	6, 688, 000	\$2, 207, 026
Other districts 2 La Plata County: California	4 3	2	392	90	30	120 390	2, 163 377	10	2, 173 377	130, 300	7, 300	0, 088, 000	6, 234 13, 918
Larimer County: Masonville	1		7	8		8	3		3			)	282
Mesa County: Sinbad Mineral County: Creede	2		39, 243	644		644	805, 202		805, 202	2, 100 77, 600	1 051 600		296 674, 975
Wontezuma County	2		1,619	218		218	741		741		1,001,000		8, 157
Montrose County: La Sal	1		138	1		1	2, 759		2, 759	16 600			4, 006
San Miguel River (Naturita)		5	100		14	14	2, 100	3	2,709	10,000			4,000
Ouray County: Red Mountain	7		1, 447	54		54	3, 119		3, 119	4 000	00,000	100 000	
Sneffels	4		33, 789 3, 369	6, 569		6, 569	110, 295		110, 295	4, 900 130, 400	88, 000 625, 600	168, 900 539, 700	26, 305 416, 232
Uncompandere	8		3, 369	159		159	27, 997		27, 997	6,000	85, 700		31, 942
Alma Placers		2			413	413		83	83			1 1	14, 514
Beaver Creek		4			1, 936	1, 936		422	422				68, 060
Buckskin	2 2	1	5, 741 885	1, 445 735	2	1, 447 735	9, 696 4, 306		9, 696 4, 306	27, 800 18, 400	118, 200 1, 800	906, 600	153, 137
Fairplay		11			13, 853	13, 853	4, 500	2, 738	2, 738	10, 400	1, 800		31, 134 486, 802
Consolidated Montgomery Fairplay Mosquito Tarrvall	6		86, 658	15, 009		15,009	9, 152		9, 152	32, 200	423, 600	5, 400	564, 602
Tarryall Pitkin County: Roaring Fork	5	2.	16, 842	1	3, 977	3,977	286, 131	433	433 286, 131	1,000	629, 800	284, 000	139, 503 272, 236
Pitkin County: Roaring Fork Rio Grande County: Summitville	i	1	14, 970	5, 497	2	5, 499	7, 186		7, 186	93, 400	800		208, 930
Routt County	1		19				28		28		700	4, 800	513
Kerber Creek	8		4, 793	60		60	41, 292		41, 292	36, 400	878, 600	663, 600	156, 448
Myers Creek	1		1				21		21		300		35
Animas	12	1	197, 048	17, 077	1	17, 078	391, 794		391, 794	572, 900	4, 248, 000	757, 000	1, 300, 677
Eureka	3		288	8		8	2,039		2,039	1,400	39, 200	23, 400 3, 600	6, 701
Ice Lake BasinSan Miguel County:	1		68	8		8	824		824	700	9, 800	3,600	1, 943
Iron Springs. Upper San Miguel.	2		19	. 5		5	917		917		3, 900		1, 088
Upper San Miguel Summit County:	7		178, 984	23, 446		23, 446	314, 903		314, 903	78, 800	3, 432, 800	780, 000	1, 356, 614
Breckenridge	5	11	82	66	1, 210	1, 276	235	315	550	100	400		45, 090
Breckenridge Green Mountain	ĭ		387	6	-,	6	2, 392 7, 768		2, 392	1,600	7, 600	322, 000	32, 560
Montezuma Ten Mile	9 2		1, 127 8, 693	20 200		20 200	7,768 30,091		7, 768 30, 091	1, 800 8, 300	195, 600 985, 600	96, 600	28, 531 215, 109
Teller County: Cripple Creek	42		377, 995	104, 455		104, 455	15, 660		15, 660	0, 000	800, 000	1, 286, 800	3, 667, 061
Total Colorado	311	68	1, 797, 386	246, 010	22, 617	268, 627	3, 092, 009	4, 202		2, 204, 000	30, 362, 000	64, 430, 000	19, 896, 623

<sup>&</sup>lt;sup>1</sup> Includes Cascade and Ute Creek district.

<sup>&</sup>lt;sup>2</sup> Includes St. Kevin and Twin Lakes districts.

#### ADAMS COUNTY

Sand and gravel handled in the washing plant of the Brannan Sand & Gravel Co. on Clear Creek, north of Denver, yielded gold as a byproduct. BOULDER COUNTY

Central (Jamestown) district.—The Wano mine was again, as in 1941, the largest producer of gold in the Central district; it was operated by the owners, who shipped crude ore to the Golden Cycle mill at Colorado Springs. Mining of gold ores ceased in May for the duration of the war, but the operator began experiments in milling fluorspar from the property and from the Emmett mine. lessee at the Smuggler group shipped gold ore to the Golden Cycle mill until operations were suspended November 12 by the Gold Mining Limitation Order. The General Chemical Co. entered the district in 1942 to mine fluorspar and incidentally shipped gold ore to the Golden Cycle mill during the latter part of the year from surface dumps on the Invincible claim. Other producers of gold in the Central district were the Black Rose group, the Emmett, and the John Jay mine. In milling fluorspar ore, 24\_tons of lead-silver concentrates were made and shipped from the Emmett mine to the smelter at Leadville.

Gold Hill district.—Slide Mines, Inc., was the leading producer of gold, silver, copper, and lead in the Gold Hill district. The company operated its Slide-Klondyke-Twin group of mines and 70-ton gravityand flotation-concentration mill continuously until August, when a change-over of most of the crew and equipment was made to operate the company tungsten mines in the Sugar Loaf district. Gold concentrates caught on burlap tables between the classifier and Wilfley tables were amalgamated, and the remainder-containing gold, silver, copper, and lead—were shipped to the Leadville smelter. Most of the ore from the other producing mines and dumps in the district was shipped to the Golden Cycle mill. Other sizable producers, in order of gold output, were the Ingram group, Gardner, Nil Desperandum, Sunshine, and the Emancipation group. Zinc-lead ore containing 7,803 pounds of zinc, 8,319 pounds of lead, 281 ounces of silver, and 14.80 ounces of gold were shipped from the Home Sweet Home to the Midvale (Utah) custom concentrator, in addition to the shipment of 1,206 tons of gold ore to the Golden Cycle mill.

Grand Island district (Nederland).—The Donora Mining Co. operated the Boulder County mine and 70-ton jig- and flotation-concentration mill at Cardinal under lease until June. About 100 tons of gold-silver-lead concentrates were produced and shipped to the Lead-The other producing mines in the district were the ville smelter.

Enterprise group, the Blue Bird, and the Golden Reward.

Magnolia district.—The producing mines in the Magnolia district in 1942, in order of gold output, were the Cash-Rebecca, Keystone, India, and Hereafter. All ore was shipped to the Golden Cycle mill.

Sugar Loaf district.—Most of the ore produced from mines and dumps in the Sugar Loaf district in 1942 was shipped to the Golden The Poorman group, worked continuously by lessees until October, was again the largest producer of gold in the district; it was followed by the Livingston, Alpine Horn, Nancy, Empress, and Herold. The silver output of the district came chiefly from the Nancy.

Ward district.—The Boston and Utica mines were operated throughout 1942 by the Ward United Mines Co. and were the leading producers of copper in the Ward district and in Boulder County. Low-grade ore concentrated at the company 25-ton concentration-flotation mill and crude smelting ore shipped to the smelter at Leadville contained (in smelting ore and concentrates combined) 1,586 ounces of gold, 1,450 ounces of silver, and 29,112 pounds of copper. Small tonnages of concentrates were also shipped to the Leadville smelter from the Columbia and Black Jack mines at Ward.

#### CHAFFEE COUNTY

Chalk Creek district.—Lessees continued to operate the Mary Murphy mine in 1942 and shipped 40 tons of gold-silver-lead-copperzinc ore to the Midvale (Utah) custom milling plant and 10 tons to the Leadville smelter. The ore contained 41.68 ounces of gold, 447 ounces of silver, 897 pounds of copper, 8,043 pounds of lead, and 16,293 pounds of zinc.

Granite district.—Ernest Dial operated the Marion Bell lode from June until September and shipped 1 ton of gold-silver ore to the Lead-ville smelter and retort and amalgam grains to the Denver Mint. The Marion Bell was the only lode operation in the Granite district in 1942. Len Savage operated his Gold Basin placer until September, using a power shovel and screening-sluicing plant. Intermittent operations on the Channel, Lost Canyon, and Independent placers produced small lots of gold, which were shipped to the Denver Mint.

Monarch district.—Production from the Monarch district comprised 82 tons of gold-silver-lead-copper ore, which was shipped by a lessee from the Madonna group to the Leadville smelter.

#### CLEAR CREEK COUNTY

Alice district (Yankee, Lincoln).—New Lombard Mines, Inc., operated the Lombard mine until August 1942 and milled the ore in the Lombard mill; the product was gold bullion shipped to the Denver Mint and 148 tons of lead-silver-gold concentrates shipped to the Leadville smelter. The Gold King mine yielded 29 tons of gold ore, which were shipped to the Golden Cycle mill at Colorado Springs.

Argentine district.—The only output from the Argentine district in

Argentine district.—The only output from the Argentine district in 1942 was from Buckley Bros. operations on the Hamill tunnel group; 506 tons of silver ore containing some silver and lead were produced, of which 375 tons were concentrated in a local custom mill and 131 tons shipped crude to the Leadville smelter.

Empire district.—In 1942 Minnesota Mines, Inc., operated continuously its Crown Prince group of mines and 250-ton (daily) flotation-cyanidation mill and was again the largest producer of gold in the county, producing over one-third of the county total. (See Minerals Yearbook, 1941, for method of ore treatment.) Copper Cone, Inc., produced 559 tons of gold-silver-copper ore from the Upper Union-Gold Fissure group; the ore was treated in the Clear Creek-Gilpin Co. mill at Idaho Springs, and the concentrates were shipped to the Lead-ville smelter. Other small producers included the Empire tunnel, Gold Dirt, and Omaha properties.

Griffith district.—The Smuggler mine, largest producer of lead and zinc in the county, was worked throughout the year by the Mile High Mining Co. Zinc and lead concentrates were produced in the Silver

Leaf mill at Silver Plume and shipped to the Amarillo (Tex.) and Leadville smelters. Fargo Mines, operators at the Fargo mines, and Wallace K. Howard at the Mendota group of mines made several small shipments of ore to the Midvale (Utah) custom concentrator. Burleigh tunnel was rehabilitated to the Phillips vein, and sampling was also done in the district by the Federal Bureau of Mines during the latter half of the year. Several shipments of dump ore were made from the Dives-Pelican group in 1942 to the Proctor Milliken mill,

east of Idaho Springs, by the Silver Plume Mines, Inc.

Idaho Springs district.—The Alma-Lincoln Mining Co. continued to operate its Lincoln-South Lincoln-Elliott Barber group and 150ton flotation mill throughout 1942 and treated 16,624 tons of ore (mill was operated 6 days a week, one shift a day), compared with 25,019 tons in 1941. The company also leased and operated the Cardigan group until April 16, 1942, and treated the ore at the Alma-Lincoln mill. Inter-Mountain Mines; Inc., operated the Dona Juanita-Maude Monroe group of mines from January 1 until May 1 and mined about 6,000 tons of ore, which were milled at the Silver Spruce mill. The Williams Mining Co. operated the Williams mine in 1942 and treated the ore at its Missouri Lake mill in Gilpin County. Until October LeRoy Giles & Co. continued to ship gold-silver ore from the Dixie No. 4 to the Ruth custom mill. Other sizable producers of gold-silver-lead-copper ores were the Shafter, Freighter's Friend, Idaho Bride, and Specie Payment group. Custom mills operating intermittently in the Idaho Springs district included the Clear Creek-Gilpin Co., Ruth, Chicago, Creek, Proctor Milliken, and Silver Spruce.

Montana district.—Virtually all production of ore from the Montana district in 1942 comprised 3,511 tons of lead-silver-gold ore from the Joe Reynolds and 2,595 tons from the Red Elephant group. Other small producers in 1942 were the Columbine and the Golden

Trail Creek district.—Lamartine Mines, Inc., operated the Lamartine-Falcon group of mines throughout the year and was the secondlargest producer of gold in Clear Creek County. About 26,060 tons of ore were treated in the company mill by flotation, supplemented by jigs in the ball mill-classifier circuit to extract free gold for amalgama-Bullion sold to the Denver Mint contained 1,436 fine ounces of gold and 372 fine ounces of silver; and concentrates shipped to the Leadville smelter contained 1,908 ounces of gold, 3,682 ounces of silver, 140,347 pounds of lead, 65,606 pounds of zinc, and some copper. Other sizable producers in the Trail Creek district were the Wheatland, Lone Tree, and Phoenix mines.

#### CUSTER COUNTY

Hardscrabble district.—The output from the Hardscrabble district in 1942 comprised 16 tons of lead ore from the Passiflora mine and 1 ton each from the Four Aces and High Kicker-Wild Girl group.

#### DOLORES COUNTY

Pioneer district (Rico).—The Rico Argentine Mining Co. operated its group of mines and 135-ton selective-flotation mill continuously in 1942 and milled 34,735 tons of zinc-lead-silver-gold-copper ore, compared with 35,666 tons in 1941. The products of the mill were lead-silver concentrates (carrying some copper, zinc, and a little gold) shipped to the Leadville smelter and zinc concentrates (carrying also silver, lead, copper, and a little gold) shipped to the Amarillo (Tex.) smelter. The zinc concentrates averaged 48.9 percent zinc, and the lead concentrates averaged 67.8 percent lead. Markey Bros. operated the Yellow Jacket group under lease and shipped crude zinc-lead ore (carrying some silver, copper, and a little gold) to custom mills in Utah.

#### EAGLE COUNTY

Red Cliff district (Battle Mountain).—In 1942 the Red Cliff district ranked first among Colorado districts in output of copper and zinc. The New Jersey Zinc Co. Empire Zinc Division Eagle mine and mill at Gilman were operated continuously in 1942; its 600-ton zinc-lead mill was operated only from June through December in 1941. The company mined and shipped very much less copper-iron-silver-gold sulfide smelting ore in 1942 than in 1941. A lessee on the Cora claim at Belden shipped 55 tons of gold-silver smelting ore in 1942.

#### EL PASO COUNTY

#### GOLDEN CYCLE MILL

The state of the s

The Golden Cycle custom mill at Colorado Springs recovered 48 percent of the total Colorado output of gold from lode mines in 1942. It treated 378,434 tons of ore averaging 0.308 ounce of gold to the ton compared with 532,127 tons of ore averaging 0.3038 ounce in 1941. Of the total ore treated in 1942, 362,460 tons were gold-[silver]-sulfotelluride ores from the Cripple Creek district (Teller County), and 15,974 tons comprised miscellaneous gold and gold-silver ores from other districts, mainly in Boulder, Clear Creek, and Gilpin Counties. As ores purchased vary in character and grade, the metallurgy is not always the same. Essential features of ore treatment are described

in this section, Minerals Yearbook, 1941.

Milling at Colorado Springs was curtailed in October by the provisions of the Gold Mining Limitation Order. A reprieve was granted to December 8, 1942, and another reprieve on that date (in response to an appeal filed with the War Production Board) permitted the mill to operate for 6 months, or until June 8, 1943, during which time equipment should be added to treat zinc-lead ores. Under the terms of this reprieve the mill was allowed to continue to treat Cripple Creek ores, with a provision also to be allowed to continue to treat siliceous gold-bearing ores to serve as a lighter-weight product to mix with iron concentrates (containing gold and silver) from the zinc-lead-iron ores. Conversion and enlargement of the flotationmill unit within the amalgamation-cyanidation plant were begun in late December 1942 and completed in February 1943. The capacity of the flotation mill (changed from bulk concentration to selective) was increased from 300 to 500 tons per day. Between February and May 1943, 4,000 tons of zinc-lead ore from Saguache, Lake, Fremont, and Clear Creek Counties were treated in the flotation unit of the plant. A further reprieve was granted June 8, 1943, permitting operations until August 8. Zinc-lead bulk concentrates from the 1,000-ton Ore & Chemical Co. "sink-and-float" mill at Leadville

(to be completed in July or August 1943) will be shipped to the Golden Cycle mill for selective concentration.

#### FREMONT COUNTY

The Monarch Galena Co. operated the Cotopaxi mine in the Cotopaxi district the last 6 months of 1942 and shipped 34 tons of zinc-copper-silver ore to the United States Smelting, Refining & Mining Co. custom concentrator at Midvale, Utah.

#### GILPIN COUNTY

Southern districts (Blackhawk, Central City, Nevadaville, Russell Gulch).—Twenty-one lode and 13 placer mines were productive in the Southern districts in 1942, as compared with 43 lode and 76 placer mines in 1941. The output of gold, silver, and copper decreased sharply in 1942, but an increase was noted in the production of lead. The Pittsburg-Notaway group of mines and 100-ton flotation mill were operated continuously under lease in 1942 by Kingmill Mines, Inc. This group yielded nearly two-thirds of the total output of gold from lode mines in the Southern districts and was the largest producer of silver and copper in Gilpin County in 1942. The goldsilver-copper concentrates were shipped to the Leadville smelter. The Queen Mineral Ranch, operated by Cole Godsey and associates, produced over half of the year's output of lead from Gilpin County. The California-Hidden Treasure Mines Co. worked the Monmouth-Kansas mine throughout the year through the Argo tunnel, sending the ore produced to the Clear Creek-Gilpin mill at Idaho Springs (Clear Creek County) for treatment. The recovery in bullion shipped to the Denver Mint and the content of concentrates sold to the Leadville smelter totaled 703 ounces of gold, 3,103 ounces of silver, 12,772 pounds of copper, and 8,883 pounds of lead. Lessees operated the New Brunswick mine and 15-ton stamp amalgamation-table concentration mill until February, when work stopped because of the high cost of labor and materials. Ore was also shipped to custom mills in Clear Creek County from the Anchor, Justice, West Notaway, Pyrenees, Rocky Mountain, and other mines and dumps in the Southern districts.

Small-scale placers working with power shovels or draglines and screening and sluicing plants in 1942 included the MacElwee, Peerless, Morgan, and Russell Gulch placers.

Northern districts.—The Perigo group was worked on a small scale by lessees during part of 1942. Most of the ore was concentrated in the Monarch 75-ton flotation mill on the property, and the gold-silver concentrates were shipped to the Leadville smelter. Other producing mines in the district were the Champion and Evergreen.

#### GRAND COUNTY

Small lots of silver-lead ore were shipped to the Leadville smelter in 1942 from the Bobtail claim in La Plata district and the Ready Cash mine near Jones Pass.

#### **GUNNISON COUNTY**

Gold Brick district.—The Carter Mines Co. continued to operate its mine and mill on Gold Creek until October 15, 1942, when production ceased in compliance with the Gold Mining Limitation Order. The ore was treated by amalgamation and by flotation and gravity concentration. Burleson Mines, Inc., operated the Raymond group and 75-ton flotation mill from January 1 to June 25, 1942; the mill recovered 46 tons of bulk lead-gold-silver concentrates, which were sold to the Leadville smelter. Crude smelting ore was shipped from the Chicago and Gold Links properties.

Taylor Park district.—In 1942 the Star and Thunderbird mines shipped 88 and 45 tons, respectively, of ore containing zinc, lead,

copper, silver, and gold to the Midvale (Utah) custom mill.

Tomichi district.—The Callahan Zinc-Lead Co., Inc., operated the Akron mine throughout 1942; operations before September were confined to development only. Zinc-lead-silver ore (286 tons) was shipped to the Midvale (Utah) custom mill.

#### HINSDALE COUNTY

Galena district.—Davis Gold Mines shipped 11 tons of lead-silver-gold concentrates, milled in 1941 from Eldorado mine ore, to the Leadville smelter in 1942. The Base Metal Corporation operated under lease the Ute and Ulay group and flotation mill and produced 263 tons of lead-silver-gold concentrates.

のでは、1000mmのでは、

#### JEFFERSON COUNTY

Placer gold and silver were the only metals produced in Jefferson County in 1942. The greatest part of the placer gold produced during the year was recovered by W. B. Kerkling from the Bertrand gravel pit and the Tresize placer. The American Smelting & Refining Co. explored the Malachite mine, near Starbuck, by diamond drilling but did not exercise its option.

#### LAKE COUNTY

#### LEADVILLE DISTRICT

The American Smelting & Refining Co. operated its Arkansas Valley lead bullion-leady copper matte smelter continuously (one furnace) in 1942 on ores and concentrates purchased from operators in virtually every active mining district in Colorado. Receipts of ore and concentrates totaled 94,659 tons compared with 121,297 tons in

1941.

The largest mining enterprise in the Leadville district in 1942 was that of the Resurrection Mining Co., which operated the Resurrection mine and 300-ton selective-flotation mill throughout 1942. In 1941 the company purchased the Yak tunnel and the mining claims of the Yak Mining, Milling & Tunnel Co. Construction was begun on a modern 250- to 300-ton flotation mill at the portal of the Yak tunnel in California Gulch; this mill was completed and production of concentrates from mine ore hauled through the Yak tunnel was started in January 1942. Total ore treated in the mill in 1942 amounted to 91,642 tons, of which 17,165 tons were dump ore from the Resurrec-

tion dump, milled for the American Smelting & Refining Co. Zinclead-gold-silver concentrates produced totaled 12,009 tons, containing 10,100 ounces of gold, 116,775 ounces of silver, 5,181,323 pounds of lead, and 7,011,312 pounds of zinc. Lead concentrates were shipped to the Leadville smelter; zinc concentrates were shipped to Amarillo, Tex. Development in 1942 consisted of 30 feet of shaft, 8,664 feet of drift, 1,181 feet of raises, and 2,753 feet of diamond drilling. To attract workers to this operation the management purchased and remodeled two large buildings in Leadville to make apartments for mine personnel. Work was commenced on a second milling unit designed to double the capacity of the 1942 milling operation; the new unit is expected to be completed and in operation in July 1943.

The California Gulch Mining & Milling Co. operated its two gravityand flotation-concentration and amalgamation mills—one 75- to 125ton capacity and one 450-ton capacity—during most of the year on ores from the Wolftone dump, Ibex dump, Valley lease, and Fortune lode. The Gold Mining Limitation Order of October 1942 forced the company to convert its small mill to the recovery of zinc and lead to remain in operation. Conversion of the larger mill to selective flotation was in progress in the early part of 1943. The John Hamm Mining & Milling, Ltd., operated its 300-ton amalgamation-gravity concentration-flotation mill the entire year on ore from the Ibex and Maid of Erin dumps. Addition of a jig plant to handle dump ores carrying zinc and lead was in progress at the close of the year. Andy Caine & Co. treated ore from the Fanny Rawlings mine by table concentration and amalgamation in the leased Norton mill. Gold-silver bullion recovered was sold to the Denver Mint: 90 tons of concentrates containing 36 ounces of gold, 537 ounces of silver, 8,632 pounds of lead, and a little copper were shipped to the Leadville smelter. The principal shippers of smelter ore to the Leadville smelter and smelters in Utah (in approximate order of tonnage) were the Breece dump, Galligher dump, Ibex, Rock Hill, New Monarch-Treasure Vault, Dolly B, Tucson, Little Jonny, Galligher lease, Fortune, Little Ellen, Golden Eagle, St. Louis tunnel, Breece, and "Lillian."

The Ore & Chemical Co. early in 1942 sampled dumps and determined 365,000 tons of mill-grade dump ore averaging 5 percent zinc and 3 percent lead; in November 1942 it began construction of a 1,000-ton "sink-and-float" mill southwest of Leadville near the Arkansas Valley smelter. The mill is scheduled for completion in July or August 1943; production of 125 tons of bulk zinc-lead concentrates (containing 15 percent zinc and 8 percent lead) a day is anticipated. The concentrates produced will be shipped to the Golden Cycle mill for selective flotation. Wartime demands for increased production of zinc and lead prompted the Federal Bureau of Mines to initiate two projects in the Leadville area designed to make available more ore for the production of these metals. The sampling of several old mine dumps in the fall and winter of 1942 proved 370.000 tons of dump ore. If funds are made available, the Bureau of Mines will drive a 2.55-mile tunnel to unwater the mines of Carbonate Hill, Evans Gulch, and Fryer Hill areas north and east of Leadville and the Downtown area within the city. Bureau of Mines engineers began planning and design studies of this project in Septem-It is anticipated that this tunnel will drain 65 to 90 percent of the mine water of the Leadville area above the 9,950-foot or

9,970-foot altitude, whichever level of the portal is chosen. An appropriation of \$1,500,000 has been approved by the Bureau of the Budget to cover costs of driving.

#### OTHER DISTRICTS

Slightly less than 400 tons of ore (mostly dry and siliceous gold, gold-silver, and silver and one small lot of lead-silver) were shipped in 1942 from mines in Lake County outside the Leadville district. Producing lode properties comprised the Amity, Dinero, and Dinero dump in the St. Kevin-Sugar Loaf district; and the Gordon-Bengal Tiger in the Twin Lakes district. Sluicing on the Derry Ranch placer in the Box Creek district recovered some gold.

#### LA PLATA COUNTY

California (or La Plata) district (Hesperus, La Plata).—Very small quantities of gold-silver ore were shipped by truck to the Leadville smelter in 1942 from the Bessie G and Nonpareil lodes. A lessee on the Mountain Lilly group shipped 19 tons of gold-silver ore to the Midvale (Utah) custom mill.

#### MINERAL COUNTY

Creede district.—The Emperius Mining Co., which in 1942 controlled nearly all mining properties in the Creede district, operated a group of mines and its 100-ton flotation mill at near capacity throughout 1942. Owing to a shortage of manpower, an average of 120 men was employed at the operation as compared with 160 in 1941. Lead-silvergold concentrates produced were shipped to the Leadville smelter. Mines shipping to the mill comprised the Amethyst group, Commodore, New York-Last Chance-Pittsburg, Equinox, Ochre, and Happy Thought. From all the above producing properties except the Happy Thought, high-grade lead-silver-gold ore was shipped direct to the Leadville smelter.

#### MONTEZUMA COUNTY

The Red Arrow Gold Corporation operated its Red Arrow mine and 25-ton amalgamation-concentration mill from January to November 17, 1942. Gold-silver bullion recovered was sold to the Denver Mint. Gold-silver-copper concentrates produced by jigging and blanket-tabling were shipped to the Leadville smelter. The Outwest Mining Co. shipped 19 tons of gold-silver ore from the Outwest property adjoining the Red Arrow.

#### MONTROSE COUNTY

La Sal district.—Lessees at the Cashin group shipped 138 tons of copper-silver ore to the Tooele (Utah) copper plant.

#### OURAY COUNTY

Red Mountain district.—Several carloads of zinc-lead-silver ore were shipped in 1942 to the Midvale (Utah) custom mill from the Beaver, Micky Breen, Barstow dump, Rico, and Ida L in the Red Mountain district. Wm. McCullough and G. A. Franz leased the Mountain

King dump in August and began trucking ore on September 1 to the Franz mill for treatment; 1,200 tons were milled, yielding 158 tons of concentrates, which were shipped to the Midvale (Utah) custom

mill for further concentration.

Sneffels district.—King Lease, Inc., operated the Camp Bird mine and the King Lease 100- to 125-ton amalgamation-flotation mill continuously in 1942. (See Minerals Yearbook, 1941, for methods of ore treatment.) A lessee on the Trust-Ruby claim shipped 5 tons of lead-silver-gold concentrates recovered from 191 tons of ore milled in the Franz custom mill. Zinc-lead-silver ore totaling 36 tons was shipped to the Midvale (Utah) custom mill from the Atlas and

Mountain Top claims.

Uncompanded district.—G. A. Franz, Inc., operated its 120-ton flotation mill 2 miles north of Ouray in 1942 on custom ores from the Mountain King dump in the Red Mountain district; Trust-Ruby in the Sneffels district; and the Bachelor, Senorita, Mineral Farm, and Wedge in the Uncompangre district. During the year, 4,187 tons of ore were milled, averaging 0.02 ounce of gold and 6.5 ounces of silver to the ton, 0.6 percent copper, 4.1 percent lead, and 4.6 percent zinc. Lead-silver concentrates were shipped to the Leadville smelter and zinc concentrates to the Amarillo (Tex.) smelter and the Midvale (Utah) concentrator. The McCullough Lease shipped 840 tons of gold-silver-copper ore to the Midvale (Utah) smelter from the Wanakah group, in addition to shipping 28 tons of gold-silver ore to the Leadville smelter from the Wanakah and American Nettie groups. The J. R. Sonza lease on the Bachelor Consolidated group of claims completed hauling the remainder of the Wedge dump to the Franz mill in 1942. Lead concentrates produced, amounting to 140 tons, were shipped to the Leadville smelter. Small tonnages of smelting ore were also shipped from the Newsboy, Senorita, and U.S. mines.

#### PARK COUNTY

Alma Placers district.—Jack Richards was the principal producer on the Alma Placers in 1942 but ceased operations in September 1942. A lessee on the Gumaer placer operated from May 18 to June 22, 1942. At both operations the gravel was excavated from open pits by power shovels and trucked to central sluicing plants for treatment. gold recovered was sold to the Denver Mint.

Beaver Creek district.—The Timberline Dredging Co. operated its electric floating connected-bucket dredge (dredge No. 1) on Beaver Creek 2 miles north of Fairplay from April 9 to October 15, 1942, when operations were stopped in deference to War Production Board Order L-208. The dredge, equipped with 84 7%-cubic foot buckets, handled 520,065 cubic yards of gravel in 1942, yielding 1,907 fine ounces of gold and 415 fine ounces of silver. Sluicing at other placers on Beaver Creek by Ray Wood and H. D. Myers recovered some gold, which was sold to the Denver Mint.

Buckskin district.—The Buckskin Joe Mines, Ltd., operated the Phillips group of mines in Buckskin Gulch and the Alma-Betts 50-ton selective-flotation mill in Mosquito Gulch throughout 1942. mill treated 5,652 tons of ore, yielding 1,560 tons of concentrates containing 1,469 ounces of gold, 9,965 ounces of silver, 33,467 pounds of copper, 133,043 pounds of lead, and 988,205 pounds of zinc. Lead concentrates carrying some gold, silver, copper, and zinc were shipped

to the Leadville smelter; zinc concentrates carrying some gold, silver, copper, and lead were shipped to the Amarillo (Tex.) smelter. A lessee on the Gold Ridge mine shipped 66 tons of zinc-lead ore to the Midvale (Utah) custom mill and 23 tons of gold-silver-lead ore to the Leadville smelter. Sluicing in Buckskin Gulch recovered a small

amount of gold.

Consolidated Montgomery district.—The Magnolia Gold Mining Co. worked the Lee Goss lode under lease throughout 1942 and produced 880 tons of gold-silver ore, containing a little copper, which was trucked to the Leadville smelter. The company 50-ton mill in Montgomery Gulch was not operated during the year. A small lot of lead-silver ore was shipped to the Leadville smelter from the Webber

group.

Fairplay district.—The South Platte Dredging Co. continued to operate (until closed by Government order October 15, 1942) its steel floating connected-bucket dredge on bench ground along the Platte River 1½ miles southeast of Fairplay. The dredge is powered by electricity and is equipped with 108 12-cubic foot buckets. The Snowstorm placer 2 miles north of Fairplay yielded a substantial output during the year. Five operators, one of which (the Timberline Dredging Co.) used a dragline (8-cubic yard bucket) and floating Bodinson washing plant (called dredge No. 2), worked the gravels on the property. Small, intermittent sluicing operations were conducted

のでは、「「は、「は、」というでは、「は、「は、「ない」というできない。「ないできないないない。」では、「ない」というできない。「ない」というできない。「ない」というできない。「ない」というできない。

at other placers on the Platte River near Fairplay.

Mosquito Creek district.—The London Mines & Milling Co. maintained production throughout 1942 from its consolidated group of mines on London Mountain and continued to be the principal metal producer in the Mosquito Creek district and in Park County. Dump and mine ore totaled 71,258 tons and was tr ated in the company 200-ton flotation- and gravity-concentration mill 7 miles west of Alma on South Mosquito Creek Besides gold—the chief metal of value the concentrates produced contained some silver, a little copper, and considerable lead and zinc and were sold to the Leadville smelter. James Redman operated his 150-ton Record mill from July 30 to August 5, 1942, and again for a few days in December on ore from the American mine. The London Butte Gold Mines Co. operated its Butte mine and 100-ton flotation mill 7 miles northwest of Alma throughout 1942 and treated 14,138 tons of ore, which made 618 tons of concentrates containing 2,720 ounces of gold, 1,685 ounces of silver, 95,004 pounds of lead, and a small amount of copper. The concentrates produced were shipped to the Leadville smelter. Several shipments of lead ore from the American, Ophir, and Hock Hocking claims were made to the Leadville smelter, and dump ore from the Orphan Boy mine was milled in the district. Reconstruction Finance Corporation granted Class A and Class B loans in 1942-3 totaling \$80,000 to mines in the Mosquito Creek, Buckskin, and Consolidated Montgomery districts, all contingent on production of zinc-lead-[silver-gold] ore.

Tarryall district.—Cooley Bros. continued to operate the Peabody-Volz group of placers 2 miles north of Como under lease from April 4 to October 15, 1942, when operations were closed by the Gold Mining Limitation Order. The 3,000-cubic yard (per day) dragline floating dredge recovered 3,858 ounces of gold and 424 ounces of silver in 1942. The Sterling Mining Co. operated its 1½-cubic yard dragline and four-

bowl land dredge on the Little Mint-Storming Jordan placer on Tarryall Creek 7 miles below Como from May 20 to September 14, 1942.

#### PITKIN COUNTY

Roaring Fork district (Aspen).—The Midnight Mining Co. operated the Midnight mine and mill continuously 6 days a week in 1942. The mine produced 9,000 tons of ore, which was treated in the company 50-ton flotation mill. The products were lead-silver concentrates (sold to the Leadville smelter) and zinc concentrates (shipped to the Amarillo (Tex.) zinc smelter). D. P. Rohlfing continued to ship to the Leadville smelter lime fluxing material carrying silver and lead from the Spar lode, Aspen, and other groups under his management. Small tonnages of crude smelting ore were shipped to the Leadville smelter from the Dorothy Louise, Mt. Ranger, and Unexpected claims.

RIO GRANDE COUNTY

Summitville district.—Summitville Consolidated Mines, Inc., operated the consolidated group of mines and 150-ton mill at Summitville continuously until August 1, 1942, when it relinquished its lease on the property. On the same day the Gold Links Mine obtained a lease to continue operating the property and maintained production throughout the remainder of the year. Crude ore milled by both operators totaled 14,970 tons, from which—in addition to amalgamation bullion and cyanide precipitates-975 tons of dry gold concentrates were made containing 3,528 ounces of gold, 5,638 ounces of silver, and 96,983 pounds of copper. Ore treatment by the Summitville operation is described under the corresponding chapter and district, Minerals Yearbook, 1941. Until November 15 the Gold Links operation was entirely amalgamation; the crude ore was run through the stamps and over amalgamation plates to remove any free gold. Amalgamation tailings were tabled and concentrates filtered and shipped to the Leadville smelter. Amalgam bullion produced was shipped to the Denver Mint. On November 15, 1942, the gradual conversion to a straight flotation mill in place of the former cyanide and amalgamation treatment was completed, and production of flotation concentrates was commenced.

#### ROUTT COUNTY

Milbank Franz shipped to a custom mill in Utah 19 tons of zinclead ore containing 0.36 ounce of gold, 398 ounces of silver, 187 pounds of copper, 877 pounds of lead, and 6,407 pounds of zinc from the Greenville mine in the Hahns Peak area.

#### SAGUACHE COUNTY

Kerber Creek district (Bonanza).—The Pratt-Bonanza Mining & Milling Co. worked the St. Louis mine under lease throughout the year and shipped lead smelting ore to the Leadville smelter and the Tooele (Utah) slag-fuming plant, zinc-lead smelting ore to the Coffey-ville (Kans.) pigment plant, and zinc-lead milling ore to the Combined Metals Reduction Co. custom mill at Bauer, Utah, and the custom concentrator at Midvale, Utah. A test run of 1,077 tons of St. Louis ore was made in the 50-ton flotation mill of the Flagstaff

Mining & Milling Co.; results were unsatisfactory. Regular shipments of zinc-lead ore were made to the custom mill at Bauer, Utah, and the custom concentrator at Midvale, Utah, from the Erie mine, operated throughout 1942 by Pickering and Olive Mines. Milling ore shipped averaged 12.6 ounces per ton of silver, 13.06 percent lead, 19.98 percent zinc, and a low content per ton of gold and copper. A substantial tonnage of lead ore containing 25.59 ounces per ton of silver, 19.15 percent lead, and minor quantities of gold and copper was shipped to the Leadville smelter. Lessees on the Rawley No. 1 mine and dump shipped some lead-silver-copper-gold ore to the Leadville smelter. Other shippers of crude smelting ore and milling ore included the Cora Group, Now What, and Minnie Lynch.

#### SAN JUAN COUNTY

こうかん はいこう こうちょう ははない かままない かんしょう しょうしゅう かんしゅう かんしゅう

Animas district.—The Shenandoah-Dives Mining Co. continued operations throughout 1942 at its consolidated group of claims on King Solomon Mountain and the Silver Lake group as a single unit, and its 750-ton selective-flotation mill on Animas River near Silverton. The mill treated 168,772 tons of ore from company mines and 2,920 tons of custom ore from other mines in San Juan County. Output from the mill totaled 4,509 tons of combined lead-copper, zinc, and iron (lead) concentrates containing in all 15,090 ounces of gold, 269,589 ounces of silver, 606,070 pounds of copper (wet assay), 2,406,020 pounds of lead (wet assay), and 961,168 pounds of zinc; the lead-copper and iron (lead) concentrates were shipped to the Leadville smelter, and the zinc concentrates (494 tons of 55.4-percent zinc content, with also gold, silver, lead, and minor copper content) to the Amarillo (Tex.) smelter. Custom ore came from the Little Fannie, Brewery tunnel, Little Nation, and Buffalo Boy mines in the Animas district; the Mountain Queen mine in the Eureka district; and the Bandora mine in the Ice Lake district. In 1942 the company entered into a 15-year contract to operate the American Smelting & Refining Co. Silver Lake unit. Ore milled in 1942 from the Silver Lake totaled 20,240 tons (included in the 168,772 tons above) assaying 0.086 ounce of gold and 1.56 ounces of silver per ton, 0.58 percent lead, 0.33 percent copper, and 0.49 percent zinc, from which 355 tons of concentrates (calculated on basis of mill recoveries) were produced. The calculated concentrates (combined lead, zinc, and iron) averaged 4.12 ounces of gold and 59.67 ounces of silver to the ton, 19.8 percent lead, 15.5 percent copper, and 15.0 percent zinc. Development in 1942 at the Silver Lake and Shenandoah-Dives groups consisted of 1,819 feet of drifts and crosscuts, 470 feet of raises, and 113 feet of diamond drilling. The Highland Mary mine and 70-ton flotation mill were operated from June 1 to November 28, 1942, when operations ceased for lack The concentrates produced (containing gold, of water for the mill. silver, copper, and lead) were shipped to the Leadville smelter. Denver Equipment Co., agent for the Pride of the West Mining Co., operated the 100-ton Pride of the West selective-flotation mill at Howardsville continuously in 1942 on company lead-zinc-gold-silvercopper ore from the Pride of the West group. Lead concentrates (containing gold, silver, copper, and some zinc) were shipped to the Leadville smelter; zinc concentrates were shipped to the Amarillo (Tex.) smelter. Development in 1942 consisted of 1,041 feet of drifts; the capacity of the mill was increased from 70 tons to 100.

lead ore was shipped to the Leadville smelter in 1942 from the Action, Austria tunnel, and Galena Champion claims; several carloads of dry gold smelting ore were shipped from the Golden Eagle property.

Eureka district.—Most of the ore produced from the mines in the Eureka district in 1942 came from the Mountain Queen claim 18 miles north of Silverton and was sold to the Shenandoah-Dives mill. About 1 car of zinc-lead ore was shipped from the Columbus property to the custom mill at Bauer, Utah. A small tonnage of zinc-lead ore recovered in development was shipped from the Mazeppa claim to the Midvale (Utah) custom mill.

Ice Lake Basin district.—The only output from the Ice Lake Basin district in 1942 was 49 tons of zinc-lead ore shipped to the Shenandoah-Dives mill and 19 tons of lead ore shipped to the Leadville smelter, all from the Bandora mine. The operators received a Recon-

struction Finance Corporation Class A loan in 1942.

#### SAN MIGUEL COUNTY

Iron Springs district (Ophir).—All the output of the Iron Springs district in 1942 was contained in small tonnages of lead-silver ore shipped to the Leadville smelter from the Butterfly-Terrible-Silver

Bell group and San Bernardo.

Upper San Miguel district (Telluride).—Telluride Mines, Inc., operated its 550-ton amalgamation and gravity- and flotation-concentration mill at Pandora 21/2 miles east of Telluride and treated 146,211 tons in 1942 compared with 193,768 tons in 1941. treated in 1942 was from the Smuggler Union, Pandora, Hermit, Montana, and Cimarron mines and the Adit and Marshall Basin dumps. Of the 14,556 tons of concentrates produced, 12,002 tons were lead concentrates shipped to the Leadville smelter; zinc concentrates were shipped to the Amarillo (Tex.) smelter. Gold bullion was also produced by amalgamation and shipped to the Denver Mint. Mine development in 1942 comprised 1,730 feet of drifts. Early in the year a unit of flotation cells was added to the mill circuit for the recovery of zinc. Alta Mines, Inc., operated the Alta-St. Louis group and 100-ton gravity- and flotation-concentration mill throughout 1942, but with some idleness due to lack of men, and produced 32,683 tons of ore yielding 3,307 tons of lead concentrates shipped to the Leadville smelter, containing 2,613 ounces of gold, 110,558 ounces of silver, 98,453 pounds of copper, 1,148,474 pounds of lead, and 435,966 pounds of zinc.

A war minerals study of the Black Bear mine by the Bureau of Mines resulted in the Metals Reserve Co. taking a 5-year lease on the property. The lease was signed June 11, 1943. The property will be opened by extension of the Treasury tunnel (Red Mountain,

Ouray County).

SUMMIT COUNTY

Breckenridge district.—Small-scale operations only were carried on at lode mines in the Breckenridge district in 1942, and most of the ore produced was shipped direct to the Leadville smelter. Shippers included the Bemrose lode, Estella Agnes, Jumbo, Royal Tiger group, and Brooks-Snyder lode.

The Blue River Co. operated its floating connected-bucket dredge at Breckenridge from May to October 1942; later the dredge was dismantled and equipment sold. The Bemrose-Bostwick in Hoosier Gulch and the John Jay group in French Gulch were worked by hydraulicking and sluicing. Testing of placer gravels in Nigger Gulch and on the Blue River and Little Pittsburg Creek recovered small

amounts of gold, which were sold to the Denver Mint.

Green Mountain district.—Walter McDaniel continued producing zinc-silver-lead-gold-copper ore of very high zinc content from his Big Four mine on Green Mountain 17 miles south of Kremmling. Output for 1942 was 387 tons of ore (shipped to the Midvale (Utah) custom mill) containing 357,997 pounds of zinc, 2,659 ounces of silver, 8,570 pounds of lead, 6.44 ounces of gold, and 1,833 pounds of copper.

Montezuma district.—The Plymouth Milling Co. worked the New York, Waterloo, and Silver King mines and 125-ton electric-powered selective flotation mill part of 1942 and produced 47 tons of lead concentrates and 63 tons of zinc concentrates which were shipped, respectively, to the Leadville and Amarillo (Tex.) smelters. on the Fisherman group operated from January 2 until September 30 and shipped to the Midvale (Utah) custom mill 179 tons of zinc-lead ore containing 5 ounces of gold, 725 ounces of silver, 37,247 pounds of lead, and 56,721 pounds of zinc. Twenty tons of lead-silver smelting ore were shipped to the Leadville smelter. Small-scale operations on the Pinacle claim produced 73 tons of crude lead-silvercopper smelting ore, which were shipped to the Leadville smelter. few lots of lead-silver smelting ore were also shipped from the Alvi No. 1, Quail, Erickson, Maid of Orleans, and Pennsylvania claims. Mining activities in this district in 1942 were encouraged by various loans totaling \$94,000 from the Reconstruction Finance Corporation and examination of several properties by Federal Bureau of Mines engineers.

The second secon

Ten Mile (Kokomo, Robinson) district.—The Wilfley Leasing Co. began production in November at its Wilfley mine and 75-ton selective flotation mill 1 mile west of Kokomo. The mill handled 799 tons of ore in 1942, composed largely of marmatite and pyrite, yielding 9 tons of lead concentrates and 128 tons of zinc concentrates which were shipped to the Leadville and Amarillo (Tex.) smelters. The opening of the property and the building of the mill were stimulated by the granting of a \$71,000 loan from the Reconstruction Finance Corporation and the construction (by the Forest Service) of a 14-foot graded access road from Kokomo to the mill. L. J. Gould and A. R. Rhine operated the Washington and Hancock group (known as the Lucky Strike group) throughout 1942 and shipped 7,820 tons of zinclead-silver-copper-gold ore to the Midvale (Utah) custom concentrator. Crude lead-silver smelting ore shipped to the Leadville smelter

totaled 74 tons.

#### TELLER COUNTY

#### CRIPPLE CREEK DISTRICT

Except for several years, Cripple Creek has been annually the leading gold-producing district in Colorado, and its total output makes it rank first among gold-producing districts. From 1891, when gold was discovered in that area, through 1942 it has yielded a total of 18,420,744 fine ounces valued at \$398,300,522, or 48 percent of the State total output of gold from 1858 to 1942, inclusive. In 1942 the district produced 104,455 ounces (39 percent of the State total) compared with

133,470 ounces (35 percent) in 1941 and 128,932 ounces (35 percent) Several factors were responsible for the decreased output in 1942, namely: Government priority restrictions regarding materials essential to mines and mills became exceedingly severe early in 1942 and have grown steadily more complicated; Selective Service regulations and attractive salaries offered by war industries created a drastic shortage of able-bodied men; the cost of labor and of mining and milling supplies increased greatly in 1942, whereas the price of gold remained fixed; and War Production Board Gold Mining Limitation Order L-208, issued October 8, 1942, has caused many mines to close. The total output of ore from Cripple Creek mines and dumps in 1942 was 377,995 tons, of which 362,460 tons were shipped to the Golden Cycle mill (operations reviewed under El Paso County). The only ore milled locally was 15,509 tons treated in the flotation mill of the Cameron Gold Mines, Inc. Cripple Creek ores generally contain gold as the only commercial metal, but some silver ore has been shipped from two or three veins in the district; a small quantity of silver is recovered annually in bullion and concentrates produced from the gold ores.

#### MINES REVIEW

Operations of the Golden Cycle Corporation, which owns and operates the Golden Cycle mill at Colorado Springs and several mines in the Cripple Creek district, are described in the following extract from its annual report to stockholders for the year ended December 31, 1942 (dated March 20, 1943):

During 1942 the Cripple Creek district shipped to the Golden Cycle mill 362,460 tons of ore with a gross [settlement] value of \$3,607,744.94 and an average value of \$9.95 per ton. This compares with 484,702 tons with a gross value of \$4,640,-419.99 and an average value of \$9.57 per ton for 1941. This large drop in tonnage was due wholly to economic conditions brought on by the war.

The United Gold Mines Co. was still the largest producer in the Cripple Creek district with the Cresson Consolidated Gold Mining & Milling Co. second and the Golden Cycle Mining Operations third. These three properties accounted for 72 percent of the ore shipped from the district and, as in previous years, lessees operating throughout the district accounted for more than 80 percent of the

total tonnage to the mill.

A large number of the company men and lessees throughout the district are older men or men who cannot get work in any other industry. The Cripple Creek district is about cleared out of younger men. The Army and Navy have received a large number of men from this district. Over forty are in the Army and Navy from the Cresson Mine alone. This labor condition affects lessees as well as the company with the result that tonnage to the mill will be greatly

decreased until the war is over.

Ajax operation.—The Ajax mine during 1942 shipped a total of 29,822 tons of ore with a gross [settlement] value of \$505,557.09 and an average value of \$16.95 per ton. The shaft was sunk an additional 105 feet to the 28th level in March. per ton. The shaft was sunk an additional 105 feet to the 28th level in March. This makes the shaft 2,900 feet deep. It still has 260 feet to go to reach the level of the Carlton tunnel. The 27th and 28th level stations were cut and crosscuts started west for the various vein systems. Due to the shortage of labor, work on both of the crosscuts has been stopped and it is doubtful if much work on these levels can be done until after the war. Most of the work at the present time is being carried on the 23d, 24th and 26th levels. The following is a summary of the development work for 1942:

Company Lèssees Shaft sinking		
Total	5 290	

Anchoria Leland operations.—The Anchoria Leland shipped 8,358 tons of ore with a gross value of \$65,170.42 and an average value of \$7.80 per ton. Practically all work done on the property during the past year was by lessees. 1,203 feet of development work was accomplished during the past year.

Index operation.—No underground work was carried out on this property during the past year. Lesses shipped 3,345 tons of dump ore with an average value of

\$4.93 per ton.

Cariton tunnel operation.—The only work done by the Golden Cycle Corporation on the Carlton tunnel during the past year was maintenance and salvage work. It was necessary to replace some timber and repair some track in order to keep the tunnel open. The Portland shaft was connected to the tunnel level by the United Gold Mines Co. and a large station cut on the tunnel level. The skips in Portland No. 2 shaft now run directly to the tunnel level. No work is contemplated in the tunnel until after the war. The Cresson Consolidated Gold Mining & Milling Co. and the United Gold Mines Co. then plan on driving two laterals; one of about 4,000 feet to the Cresson shaft and one of 5,000 feet to the Vindicator shaft. The flow of water from the tunnel has held steadily to about 5,400 gallons per minute throughout the year. It is well to point out at this time that a large percentage of all mine ore being shipped to the mill from the Cripple Creek district at this time has been made available by the Carlton tunnel. Without the drainage afforded by the Carlton tunnel, there would be no ore coming from the Ajax and Portland and very little from the Cresson. It is even doubtful if these properties could operate at all under present conditions.

The annual report of the United Gold Mines Co., an operating and holding company for property scattered throughout the Cripple Creek district, for the year ended December 31, 1942 (dated February 15, 1943), gives the following details on operations at individual mines:

#### GENERAL MANAGER'S REPORT

Production by the company and lessees was 119,346 tons, with an average value of \$8,44 per ton and a gross [settlement] value of \$1,007,693. Of this amount the company accounted for 21,007 tons with an average value of \$6.68 per ton and a gross value of \$140,314, while the lessees accounted for 98,339 tons with an average value of \$8.82 per ton and a gross value of \$867,379.

with an average value of \$8.82 per ton and a gross value of \$867,379.

The Portland No. 1 and No. 2 shafts, the Vindicator, and the Rose Nicol shafts were operated by the company, largely for the accommodation of split-

check lessees.

The shortage of company men and lessees has steadily grown worse throughout the year. The big blow came with the War Production Board's order closing all gold mines in October 1942. While this order was later modified, nevertheless it caused a regular exodus from this district to various defense plants, base metal mines, and other industries of a like nature, until at the present time we are left with older men or men who are not capable of doing any work except leasing in this district. In January 1942 there were 489 men working on the various properties of the United Gold Mines Co.; January 1943 shows 100 men working on these same properties. This gives some idea how employment has dropped off in this district.

The Portland No. 2 shaft was completed to the [Carlton] tunnel level and a 50-foot sump sunk below this level during the year. A large station was cut in order to handle the muck from all future work at the Carlton tunnel level. Part of the equipment, which was located at the mouth of the tunnel, has now been moved onto this station in preparation for driving both the Cresson and Vindicator laterals of the tunnel when we have the available manpower and this will

not be until after the war.

Both the Portland No. 1 and No. 2 shafts were operated on company account; No. 1 shaft for the accommodation of split-check lessees, and No. 2 shaft mainly for company work. A large amount of clean-up and repair work was carried out in the lower levels of No. 2 shaft. The 31st, or the old winze level, was connected through to the shaft and a station cut. Track and pipe have been installed on this level, in preparation to do some development work when the necessary manpower is available. Considerable development work was accomplished both by the company and lessees. The company opened several small chutes of ore on the 27th and 29th levels and these are being mined to a limited extent at the present time. A considerable tonnage of low-grade ore was hoisted from a large cave on the 27th level. In fact, more ore was shipped on company account from the Portland during 1942 than for a good many years past.

There are six sets of lessees working underground on the Portland and three sets of dump lessees. All of these made a fair production during the year.

The Vindicator-Cycle group.—The Vindicator shaft was operated by the company throughout the entire year. There are seven sets of lessees operating underground on this property at the present time. The Theresa and Hull City shafts were closed down about the middle of the year, due to a lack of lessees. During the year the Vindicator sold a total of 32,212 tons of crushed rock. This was the best year we have had as far as the crushed rock business is concerned in a number of years.

 $\tilde{R}ose$  Nicol.—The Rose Nicol shaft produced 13,316 tons with a gross value of \$163,134. Of this amount the lessees produced 8,667 tons with a gross value of \$136,154, and the company accounted for the balance of 4,649 tons with a gross

value of \$26,980.

In spite of the shortage of both company men and lessees, the company accomplished 1,100 feet of development work and the lessees accounted for 1,145 feet, making a total of 2,245 feet on the property for the year. Some good ore was opened which is now being mined. There are seven sets of lessees operating through the Rose Nicol shaft and one set through the Trail tunnel.

Shurtloff-Findley.—This property, which had been under lease to the Golden Conqueror Mines, Inc., for a number of years, was closed down in December, due chiefly to the labor shortage. In previous years a good production came from

this mine.

The Wild Horse, Deadwood, and other miscellaneous properties are all idle and there is very little chance that any work can be done on them until after the war. The Tennessee Mines Co. is operating the Patti Rosa shaft and making some production. One set of lessees are also working on the Kalamazoo. There are not more than ten men working on all the miscellaneous United Gold Mines properties. Two years ago there were probably 250 men working on this same ground.

The Teller County Air Co., which the United Gold Mines Co. owns, has virtually lost all its business since its chief market for compressed air was the small

scattered operations throughout the district.

Production of company ore by United Gold Mines Co. in 1942

Mine	Net tons	Gross value <sup>1</sup>	Company ore cash receipts	Average gross value per ton 1
Vindicator	2, 442	\$11, 399	\$4,058	\$4. 67
	4, 649	26, 980	11,939	5. 80
Rose Nicol. Portland. No, 2 Plant.	6, 944	71, 435	43, 006	10. 29
	6, 972	30, 500	9, 935	4. 37
	21,007	140, 314	68, 938	6. 68

<sup>1</sup> Settlement value.

#### Production of lessee ore of United Gold Mines Co. in 1942

Group	Net tons	Gross value 1	Royalties received	Lessees' receipts	Average gross value per ton 1
Vindicator Rose Nicol Portland Theresa Hull City Bull Hill Group	52, 386 8, 667 8, 440 4, 254 1, 619 22, 973 98, 339	\$342, 364 136, 154 139, 990 35, 077 15, 006 198, 788 867, 379	\$58, 255 42, 490 46, 425 10, 208 4, 401 14, 917	\$108, 831 47, 622 52, 005 9, 437 4, 058 83, 764 305, 717	\$6. 54 15. 71 16. 59 8. 25 9. 27 8. 65

<sup>&</sup>lt;sup>1</sup> Settlement value.

Production of properties of United Gold Mines Co. before and after organization of the company (May 15, 1902) to December 31, 1942

는 보고 하게 하고 하셨다. 그들은 사이 하는 것도 하는 것은 것은 것이다. 그런 것이 되었다. 	Net tons	Grossvalue <sup>1</sup>
Ore mined before consolidation	26, 310 2, 339, 411	\$456, 806 24, 382, 719
Total to Dec. 31, 1942.	2, 365, 721	24, 839, 525

<sup>1</sup> Settlement value.

The annual report of the Cresson Consolidated Gold Mining & Milling Co. for the 12 months ended December 31, 1942 (dated February 1, 1943) says—

#### PRESIDENT'S REPORT

Herewith is annual statement of The Cresson Consolidated Gold Mining &

Milling Co. for the twelve months ended December 31, 1942.

Operating gain for 1942 was \$55,754, compared to \$122,903 in 1941, a decrease of \$67,149. Many factors, chief of which are hereafter set out, caused the large decrease in gain for 1942 compared to 1941.

Company ore produced during 1942 had a gross value of \$246,596 and an average per ton gross value of \$6.18, compared to a total gross value of \$363,821 in 1941, with an average per ton gross value of \$6.84.

Ore produced by lessees operating under split-check and royalty leases for 1942 had a gross value of \$765,573 and an average per ton value of \$12.48, compared to 1941 with a total gross value of \$973,659 and an average per ton gross value of \$12.65.

Total gross value of all ores produced by both the company and lessees during

1942 was \$1,012,169, compared to \$1,337,480 in 1941, a decrease of \$325,311.

Early in 1942 the priority restrictions insofar as securing materials necessary for gold mining became exceedingly severe and have grown steadily worse. On October 8, 1942, the Mining Branch of the War Production Board, Washington, D. C., issued an order closing down all "nonessential" gold mines in the United States, its territories, or possessions.

#### SUPERINTENDENT'S REPORT

The following is a summary of the development work for twelve months, ending December 31, 1942:

	Development			
Drifts and crosscuts: Company		•	Feet 1, 707	Feet
Hart group			1, 707	
Lessees			1, 317	0.0=
Raises and winzes:				3 <b>, 257</b>
Company	:		363	
Lessees			1, 171	1 704
				1, 534
				4. 791

Shortage of men during the past year resulted in the smallest production from the mine in a number of years. From the beginning of the year, labor shortage became progressively worse, reaching its climax when the War Production Board issued the order closing all gold mines. The bottom then dropped out of our man power. While the order was modified early in December just before the date set for a complete close down, the damage had been done and we were left with a small number of older men and lessees; the cream of our man power having left for various other industries paying much higher wages than it is possible for

but for various of the find states paying intending wages than it is possible for us to pay. The armed forces have also taken over forty of our younger men.

During the past year, the nineteenth level, which was under water until the later part of 1941, was cleaned up. Track and pipe lines were installed and some development work accomplished. Two bodies of medium grade ore were

opened which we are mining at the present time. Some development work was also done on various other levels of the mine and some small bodies of ore were

opened.

There are eighteen sets of split-check lessees working through the Cresson shaft; however, these lessees have about fifty percent of the men which would be normally employed on these blocks of ground. Most of these lessees produced during the past year a good tonnage of ore considering the handicap they were forced to work under. One of the most serious aspects of the shortage of men by the Company and lessees is the lack of development work. At the present time we are doing less work of this kind than at any time in the history of the mine. Development work is very necessary in order to open up new bodies of ore upon which the mine must depend for its future production.

The Gold Sovereign shaft was closed down in August of this year, due to a lack

of lessees. This shaft had been worked entirely by split-check lessees.

Work on the Hart group on Bull Hill, which we were carrying on through the Empire State shaft of the Empire Lee Mining Co., was also suspended during the early summer. There is much more work that should be done upon this

piece of ground when conditions permit.

The water level in the Cresson shaft is now sixty-five feet below the nineteenth level, and according to the present rate of drainage, it will be at least eighteen months before it would reach the twentieth level or the bottom level of the mine. The twentieth level is 700 feet above the level of the Carlton tunnel; but as I stated in last year's report, it will be necessary to drive a lateral from the Carlton tunnel into the ground in order to give complete drainage in the Cresson property. We had planned to start this lateral during the past year but this was impossible due to the shortage of labor.

The average cost per ton shipped by company and the lessees during 1942 was

\$3.1177 on a total of 101,203 tons.

9.1177 On a total of 101,200 tons.	Carrier States
ederal taxes	\$0. 119
tate income taxes	. 000
tate and county taxes	.`15
ales, service, and use tax	. 01
ederal excise tax	003
apital-stock taxesocial-security taxes	. 004
ocial-security taxes	. 01
fiscellaneous taxes	. 002
	<del> </del>
	. 32
Inemployment-compensation insurance	. 019
omnonsation insurance	063
bonoid fire incurrence	010
dusiness insurance	. 02'
arlton interests group insurance	. 010
alary of officers and directors	. 04
eneral expense	. 054
Ining operations	2. 56
grand operations and the second secon	
	2, 79
	3, 113

Production of Cresson Consolidated Gold Mining & Milling Co., 1903 to December 31, 1942

The state of the s					18 - 57
Period		Dry short tons	Gross value	Freight and treatment	Net value
1903 to Dec. 31, 1941 1942: Company ore Lessee ore		3, 093, 175 39, 872 61, 331	\$45, 178, 658 246, 596 765, 573	129, 246 286, 947	\$30, 348, 159 117, 350 478, 625
1903 to Dec. 31, 1942		3, 194, 378	46, 190, 822	15, 246, 688	30, 944, 134
Period	Royaltie received by com- pany	Amou	gross val	ue net value	Dividends
1903 to Dec. 31, 1941	\$245, 55	6 \$233,0	\$14. 6. 12.	18 2.94	\$13, 479, 273 } 73, 200
1903 to Dec. 31, 1942	Ψ210, 00		14.		<sup>2</sup> 13, 552, 473

Settlement value.
 Represents 29.34 percent of gross value and 43.80 percent of net value.

Shipments from the Stratton properties in 1942 totaled 23,714 tons of ore, which had a total gross settlement value of \$325,781.11 or an average settlement value of \$13.74 per ton. Most of the ore was mined by lessees under the split-check system. About half of the ore produced was dump ore shipped by the Regain Corporation from three groups of dumps on Bull Hill. The principal producers of mine ore were the Alie Bell Mining Co., A. B. Cobb, Longfellow Mining Co., Jess Vetter, and J. E. Vanderwalker.

Cameron Gold Mines, Inc., operated its group of mines and 100-ton flotation mill until June 1942, when operations ceased and the corporation started liquidation proceedings. Ore treated totaled 15,509 tons yielding 702 tons of concentrates containing 1,698 ounces of gold and 1,132 ounces of silver; the concentrates were shipped to the Leadville smelter. In approximate order of gold output the Empire Lee, Acacia, Free Coinage, Forest Queen, and Jerry Johnson continued to be important producers in 1942 until December 10. Some of the other producing mines and dumps were the Black Belle, Cardinal-Great West, Dr. Jack Pot, Economic dump, Joe Dandy, New Gold Dollar, and Strong.

# GOLD, SILVER, COPPER, LEAD, AND ZINC IN THE EASTERN STATES

(MINE REPORT)

By A. J. MARTIN

#### SUMMARY OUTLINE

	Page		Page
Summary		Review by States-Continued.	
Calculation of value of metal production	350	New Jersey	
Mine production by States	353		355
Mining industry	353	North Carolina	357
Ore classification	354	Pennsylvania	
Metallurgic industry	354		
Review by States	355	Tennessee	358
Alabama	355	Vermont	360
Georgia	355	Virginia	360

#### SUMMARY

The principal copper, zinc, and zinc-lead mines in the Eastern States operated at or near capacity throughout 1942, and their total output of copper and zinc increased over 1941. Zinc production in New York and Tennessee and byproduct copper production from the Cornwall iron mine in Pennsylvania were larger than in any previous year. Copper production increased in Tennessee also but decreased in North Carolina. The output of zinc in New Jersey—secondlargest zinc-producing State in the United States during the vear-was nearly the same as in 1941, and that in Virginia decreased. Although fixed or ceiling prices on copper, lead, and zinc prevailed throughout 1942, the Government premium-price program, effective February 1, and funds obtainable through Federal lending agencies provided incentives for expansion in mining, development, and prospecting. An old zinc-lead mine in Virginia was reopened during the year, and a newly developed zinc mine in Tennessee and an old copper mine in Vermont were being equipped and prepared for operation as the year ended. Gold production in the Eastern States decreased heavily. Two mines, one in North Carolina and one in South Carolina, yielded 77 percent of the total in 1942 and 83 percent in 1941. Both these mines suspended operations before the end of October 1942, and nearly all the gold output during the last 2 months of the year (averaging 218 ounces monthly) was incident to the mining of iron and copper. Small lode and placer mines exempted from Gold Mining Limitation Order L-208 issued by the War Production Board on October 8, 1942, produced only 3 percent of the total gold output of the Eastern States in 1941 and 4 percent in 1942. The lead output in both years came from mines producing zinc as the metal of chief value, and the silver production was that recovered as a byproduct of the mining of other metals.

All tonnage figures are short tons and "dry weight"; that is, they do not include moisture.

The value of the metal production herein reported, except that of zinc in New Jersey, has been calculated at the following prices. value of the New Jersey production is the total value of the zinc recoverable as metal and oxide after freight, haulage, smelting, and manufacturing charges are added.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zinc 4
1938 1939 1940 1941 1941	Per fine ounce \$35.00 35.00 35.00 35.00 35.00	Per fine ounce  5 \$0. 646+  6. 678+  7. 711+  7. 711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057 .067	Per pound \$0.048 .052 .063 .075

¹ Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.

² Treasury buying price for newly mined silver.

² Treasury buying price for newly mined silver.

³ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.

⁴ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.

⁵ \$0.64646464.

これのは、これのできます。 これのこれのは、これのこれのこれのこれのできないのできないのできないのできないのできないのである。

Annual figures for the 5 years ended with 1942 are given in the table The figures for tonnage of ore sold or treated do not include magnetite ore containing pyrite and chalcopyrite, from which copper, gold, and silver were recovered as byproducts.

Mine production of gold, silver, copper, lead, and zinc in the Eastern States, 1938-42, in terms of recovered metals

	Mines producing		Ore sold or treated	Gold (lode and placer) <sup>2</sup>		Silver (lode and placer)	
Year	Lode	Placer	(short tons) 1	Fine ounces	Value	Fine ounces	Value
1938 1939 1940 1941 1942	51 47 40 43 36	26 24 18 14 17	3, 159, 880 3, 409, 619 3, 674, 815 3, 780, 397 4, 166, 226	19, 928 17, 414 18, 456 21, 982 14, 699	\$697, 480 609, 490 645, 960 769, 370 514, 465	94, 945 94, 083 102, 825 106, 051 105, 307	\$61, 380 63, 862 73, 120 75, 414 74, 885
Copper		Lead		Zinc			
1 cai	- ·						Total value
	Pounds	Value	Short tons	Value	Short tons	Value	

Excludes magnetite-pyrite-chalcopyrite ore from Pennsylvania.
 Includes placer gold as follows—1938: 667 ounces; 1939: 413 ounces; 1940: 452 ounces; 1941: 203 ounces;
 1942: 69 ounces.

3 Placer silver did not exceed 39 ounces in any year during the 5-year period.

Gold.—The old Haile mine in Lancaster County, S. C., near Kershaw (operated only 9 months in 1942) yielded 50 percent of the total mine output of gold in the Eastern States in 1942 and 69 percent in 1941. The Condor mine near Waxhaw, Union County, N. C.—second-largest producer of gold in both years—contributed 27 percent of the total in 1942 and 14 percent in 1941; the mine was closed in October 1942. The only other important producer of gold in 1942 was the Cornwall mine in Lebanon County, Pa., which yields gold, silver, and copper as a byproduct of iron mining. Changes in output of gold in the various States in 1942 comprised increases of 833 ounces in North Carolina and 77 ounces in Pennsylvania and decreases of 7,684 ounces in South Carolina, 281 ounces in Georgia, 131 ounces in Virginia, 68 ounces in Tennessee, and 29 ounces in Alabama. The estimated output of gold in the Southern Appalachian States from 1799 to 1942 is recorded as follows:

Mine production of gold in the Southern Appalachian States, 1799-1942

State	Period	Fine ounces	Value	State	Period	Fine ounces	Value
Alabama	1830-1942 1830-1942 (¹) -1942	49, 489 870, 509 6, 102	\$1, 198, 775 18, 083, 662 163, 940	South Carolina	1829-1942 1831-1942 1828-1942	318, 654 20, 197 167, 364	\$7, 556, 980 454, 525 3, 570, 719
North Carolina	1799–1942	1, 104, 430	24, 322, 523	Total	1799-1942	2, 596, 751	55, 351, 124

<sup>1</sup> Year of first production not recorded.

Silver.—The silver recovered from ores and gravels mined in the Eastern States in 1942 comprised 55,926 ounces derived from copper and iron (magnetite-pyrite-chalcopyrite) ores, 41,773 ounces from zinc-lead ores, 7,606 ounces from gold ores, and 2 ounces from placer

gravel.

Copper.—The upward trend in copper production in the Eastern States which began in 1939 continued in 1942, when the output increased 5 percent over 1941 and was 35 percent above that in 1938. The quantity of copper recovered in 1942 from magnetite-pyrite-chalcopyrite ore of the Cornwall mine in Pennsylvania was the highest annual output to date, and that recovered from copper ore increased slightly. As the three mines that produced nearly all the copper output of the Eastern States in 1942 are in different States (North Carolina, Pennsylvania, and Tennessee), it is not possible to show the production separately by States without disclosing that of each mine; the combined output of the three States is shown under Tennessee in the following table. Copper ore yielded, in recovered metals, about 0.0003 ounce of gold and 0.05 ounce of silver to the ton of crude ore. Copper concentrates from the Cornwall ore contained some recoverable gold and silver.

Lead.—The mine output of recoverable lead in the Eastern States was 4,475 tons in 1942 compared with 5,513 tons in 1941. The figures for 1941 include some lead contained in concentrates shipped from mine stocks accumulated in previous years, whereas those for 1942 represent the recoverable metal in concentrates actually produced during the year. Comparing actual mine production in 1941 (4,039 tons) with that in 1942 shows an increase for 1942 of 11 percent.

Zinc-lead sulfide ores from the Austinville mine in Virginia and the Balmat in New York continued to yield the bulk of the lead output; the rest came from lead carbonate ore from the Embree mine (producing also zinc carbonate), mixed zinc-lead carbonate and sulfide ore from the Bunche's Hollow (Imperial) in Tennessee, and zinc-lead

sulfide ore from the Valzinco in Virginia.

Zinc.—Zinc mine operators in the Eastern States made determined efforts to obtain maximum production from developed ore reserves in 1942 and to find and develop ore bodies upon which to draw to help meet the anticipated continued heavy demand for zinc for the duration of the war. Several of the mines made the largest annual production in the history of their operation, and the Eastern States total output of recoverable zinc was the largest on record—199,809 tons in 1942 compared with 191,310 tons in 1941. The figures for 1941 include some zinc contained in concentrates shipped from mine stocks accumulated in previous years, whereas those for 1942 represent the recoverable metal in concentrates actually produced during the year. Comparing actual mine production in 1941 (186,880 tons) with that in 1942 shows a 7-percent increase for 1942. The output in New York increased 19 percent and in Tennessee 22 percent; in New Jersey it varied little from 1941 (0.28 percent increase); and in Virginia actual production (not shipments) decreased 13 percent. About 95 percent of the total zinc output in the Eastern States in 1942 was produced without benefit of the Government premium. It is unlikely that this high percentage can be maintained in 1943 if the 8.25-cent ceiling price remains unchanged. The developed. high-grade ore bodies are being depleted at a rapid, rate, necessitating much new prospect drilling and mine development, as well as the mining of lower-grade ores. Increases in production costs thus incurred, which cannot be absorbed by the mining companies, probably will be compensated by quota adjustments. Also, production from new enterprises will be paid for at premium prices. The Valzinco zinc-lead mine in Spotsylvania County, Va., which was reopened and equipped with a 100-ton mill in 1942, began producing before the end of the year; and the American Zinc Co. of Tennessee plans to open a newly developed mine at Jefferson City, Tenn., during the first part of 1943.

一般の一般のです。 これのできる いまんかいちょう かんかん こうしゅうしゅう

#### MINE PRODUCTION BY STATES

Mine production of gold, silver, copper, lead, and zinc in the Eastern States in 1942, by States, in terms of recovered metals

	Mines	prod	uc-					Gold			Silver	
State	iı	ng		Ore (sl		Fir	ie c	unces	Total	Fine or	inces	Total
	Lode	Pla	cer		i,	Lod	e	Placer	value	Lode	Placer	value
Alabama Georgia New Jersey	$\begin{bmatrix} 1\\3\\1\end{bmatrix}$		15	643,	35 75 766		1 15	15	\$35 1,050	6	<u>î</u>	\$5
New York North Carolina Pennsylvania South Carolina Tennessee Virginia	3 7 1 4 11 5		i	548, 40, (1)	816 429 270 854	4, 07 2, 49 7, 82 15	9 24	53	142, 695 87, 465 273, 840 5, 565 3, 815	40, 012 8, 259 15, 501 5, 064 34, 671 1, 792	i	28, 453 5, 873 11, 023 3, 601 24, 655 1, 275
Total, 1941	36 43		17 14	<sup>2</sup> 4, 166, <sup>2</sup> 3, 780,		14, 63 · 21, 77		69 203	514, 465 769, 370	105, 305 106, 036	, 2 15	74, 885 75, 414
		Cop	per			Le	ad			Zine		
State	Pound	is	V	alue -		nort ons		Value	Short tons	Value	Tot	al value
Alabama Georgia												\$35 1,055
New Jersey New York North Carolina Pennsylvania	(4) (4)			(4) (4)		2, 434	\$3	26, 156	94, 040 45, 807	* \$16, 517, 14 8, 520, 10	)2   8	5, 517, 146 3, 874, 711 5 148, 568 5 98, 488
South Carolina Tennessee Virginia	1, ( 4 28, 348, 55, (		4 3, 4	\$121 430, 108 6, 655	`	238 1, 803		31, 892 41, 602	43, 971 15, 991	8, 178, 60 2, 974, 32	6 6 6 1	277, 562 1, 670, 826 3, 227, 673
Total, 1941	28, 404, 6 27, 132, 6			136, 884 201, 576		4, 475 5, 513		99, 650 28, 482	199, 809 191, 310	36, 190, 18 29, 484, 42		0, 816, 064 1, 159, 265

Ore is magnetite-pyrite-chalcopyrite, flotation copper concentrates from which yielded gold, silver, and copper; Bureau of Mines not at liberty to publish figures for ore and copper.
 Excludes magnetite-pyrite-chalcopyrite ore from Pennsylvania.
 Estimated smelting value of recoverable zinc content of ore after freight, haulage, smelting, and manufacturing charges are added.
 North Carolina and Pennsylvania included under Tennessee; Bureau of Mines not at liberty to publish experience durges.

separate figures.

§ Excludes value of copper, which is included under Tennessee.

§ Includes also value of copper from North Carolina and Pennsylvania.

#### MINING INDUSTRY

The total output of ores yielding gold, silver, copper, lead, or zinc in the Eastern States, excluding the magnetite-pyrite-chalcopyrite ore from Pennsylvania, increased 10 percent in 1942 over 1941 to 4,166,226 tons, the highest annual production in the 37-year period (1906-42) for which complete data are available. Eight large, well-equipped zinc and zinc-lead mines in New Jersey, New York, Tennessee, and Virginia and three copper-iron sulfide mines in the Ducktown (Tenn.) district together yielded 96 percent of the total ore in 1942; all were operated at a high production rate, and some were operated beyond their normal capacity to provide the maximum quantity of metals needed for war purposes. War conditions caused a general shutdown of mines producing gold ores. The copper, zinc, and zinclead ores of the Eastern States yield byproducts (besides gold and silver), the value of which would have to be considered to show the

full value of the crude ore mined. Copper-iron ore from Tennessee and zinc-lead-pyrite ore from New York yield pyrite concentrates that are used in the manufacture of sulfuric acid, and sulfuric acid is also made from gases produced in roasting zinc sulfide concentrates from zinc and zinc-lead ores of Tennessee, New York, and Virginia. New Jersey zinc ore yields a residue which is further treated for the recovery of other metals; and zinc ore milled in Tennessee yields a commercial tailing, some of which is sold for its lime content and some for use in concrete. The quantity of the various types of ore mined in the Eastern States is shown in the table that follows.

#### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

Ore sold or treated in the Eastern States in 1942, with content in terms of recovered metals

Source	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (short tons)	Zine (short tons)
Dry and siliceous gold ore	106, 555 843, 995 (3) 4, 627	11 861 260 2, 499	7, 606 40, 425 15, 501	1,000 128,351,000 (1)	200	(2)
Lead ore Zinc ore Zinc-lead ore	2, 364, 229 846, 820	10	41, 773	52,000	4, 275	150, 270 2 49, 539
Total, lode mines Total, placers	4 4, 166, 226	14, 630 69	105, 305 2	28, 404, 000	<b>4</b> , 475	199, 809
Total, 1941	4 4, 166, 226 4 3, 780, 397	14, 699 21, 982	105, 307 106, 051	28, 404, 000 27, 132, 000	4, 475 5, 513	199, 809 191, 310

(人間を開発を見るこれがリーマンと、「同日本の経験を記している」というないとなる方式の表現を表現を対していることとなって、ことできます。

separate figures.

Bureau of Mines not at liberty to publish separate figures for ore and copper.

Excludes magnetite-pyrite-chalcopyrite ore from Pennsylvania.

#### METALLURGIC INDUSTRY

All the principal producing base-metal mines in the Eastern States except the Fontana copper mine in North Carolina have concentrating mills at or near the mines, but a considerable tonnage of copper ore is smelted direct, and some of the crude zinc ore is shipped to oxide plants. The ore from the Fontana mine is shipped to the Tennessee Copper Co. plant in Tennessee. The methods of treatment used in the various mills and other operating details, including the tonnage and grade of concentrates produced by some of the mills, are given in the Review by States that follows. Most of the concentrates are shipped to smelters operated by the companies that own the mines. The principal development in zinc-ore concentration during the past 7 years has been the increased tonnage treated at Mascot, Tenn., by the differential-density process of gravity concentration. This process is used as the first step in concentration and discharges a large part of the crushed mine ore at a coarse size as a finished tailing, thus reducing the quantity to be treated by jigging, fine grinding, and flotation.

The methods of recovering gold and silver in the Eastern States in 1942 are shown in the following table.

Copper from magnetite-pyrite-chalcopyrite ore included with that from copper ore.
 Zinc from copper ore included with that from zinc-lead ore; Bureau of Mines not at liberty to publish

Mine production of gold and silver in the Eastern States in 1942, by methods of recovery, in terms of recovered metals

Method of recovery	Material treated (short tons)	Gold (fine ounces)	Silver (fine ounces)
Ore and old tailings amalgamatedOre cyanided Concentrates smelted <sup>1</sup>	371 105, 726 77, 032 20, 812	119 11, 302 2, 668 541 69	87 7, 312 91, 945 5, 961 2
Total, 1941		14, 699 21, 982	105, 307 106, 051

<sup>&</sup>lt;sup>1</sup> Excludes material containing no recoverable gold or silver. The totals for concentrates and direct-smelting ore shipped were 703,771 and 99,296 tons, respectively.

#### REVIEW BY STATES

#### ALABAMA

A lessee at the Hog Mountain mill dump in Alabama near Alexander City, Tallapoosa County, recovered 1 ounce of gold from old tailings in 1942.

#### **GEORGIA**

There was little activity at gold mines in Georgia in 1942. Of the 30 ounces of gold produced, 15 ounces came from scattered placer mines in Cherokee and Lumpkin Counties and 15 ounces from lode mines on the Brand Estate and Dean Hole properties in Cherokee County and the Russell property in Paulding County. Seven ounces of silver were recovered from the gold bullion and retorts shipped during the year.

NEW JERSEY

Zinc production in New Jersey was approximately the same in 1942 as in 1941. The producing mines in both years were the Mine Hill and the Sterling Hill at Franklin and Ogdensburg, respectively, in Sussex County. The commercial minerals in the ore are franklinite, willemite, and zincite. Each mine is equipped with a mill. In treatment, the franklinite (an iron-manganese-zinc oxide mineral) is removed from the crushed ore by magnetic separators, and the willemite and zincite are concentrated on jigs and tables. The concentrates are shipped to company plants at Palmerton, Pa. Part of the zinc is recovered as metal and part in oxide.

The value of the New Jersey output of zinc given in the table of this chapter under the heading Mine Production by States is the combined value of the zinc recoverable in both metal and oxide after freight, haulage, smelting, and manufacturing charges are added.

New Jersey has a few deposits of copper ore, but none has been worked for many years. At Carteret and Perth Amboy are copper and lead smelters and refineries that treat ores, scrap, byproducts, and bullion from various States and foreign countries.

#### **NEW YORK**

The mine production of recoverable zinc in New York increased 19 percent in 1942 over 1941, lead 16 percent, and silver 6 percent. The silver and lead and most of the zinc came from the Balmat mine

in St. Lawrence County about 8 miles southeast of Gouverneur. This mine and the Edwards about 12 miles northeast of the Balmat are owned and operated by the St. Joseph Lead Co. The Balmat ore contains zinc, iron, and lead sulfides, and some silver is associated with the lead; it is mined through a 2,655-foot inclined shaft (vertical depth, about 1,300 feet) and treated in the selective flotation plant at the mine. The daily capacity of the mill at the end of 1942 was 1,200 tons. The mill feed in 1942 totaled 380,893 tons (44,622 tons more than in 1941); it yielded 4,165 tons of lead concentrates containing 60.23 percent lead and 10.12 ounces of silver to the ton, 62,560 tons of zinc concentrates containing 56.47 percent zinc, and 77,087 tons of pyrite concentrates containing 41.18 percent iron and 49.41 percent The Edwards mine and flotation mill were also operated at a higher rate than in 1941. The mine has a vertical shaft to the 1,500-foot level and an inclined shaft 1,361 feet long, of which 149 feet were sunk in 1942. Ore treated totaled 151,403 tons yielding 25,229 tons of zinc concentrates containing 58.97 percent zinc. zinc concentrates from both mills were shipped to the company electrothermic zinc-reduction plant at Josephtown, Pa. Part of the lead concentrates from the Balmat mill were shipped to the company smelter at Herculaneum, Mo., and part to the U.S. Metals Refining Co. plant at Carteret, N.J. The pyrite concentrates were sold to sulfuric acid plants. The Universal Exploration Co. operated its Hvatt zinc mine and 200-ton flotation mill near Emeryville from January to August; mining and milling were suspended the rest of the year but were resumed in February 1943. The concentrates produced were shipped to the Donora (Pa.) smelter.

Development of the zinc and lead deposits in St. Lawrence County was begun in 1911, and the State became an important producer of zinc in 1915. The following table gives the annual output of silver, lead, and zinc from 1928 to 1942.

Mine production of silver, lead, and zinc in New York, 1928-42, in terms of recovered metals <sup>1</sup>

Year	Ore and old tailings treated (short tons)	Silver (fine ounces)	Lead (short tons)	Zinc (short tons)	Total value
1928 1929 1930 1931 1932 1933 1934 1935 1936 1937 1938 1939 1940 1941 1942	125, 192 149, 183 270, 601 269, 582 189, 679 180, 670 282, 952 295, 179 377, 451 464, 870 385, 600 420, 000 432, 219 488, 079 548, 816	26, 406 21, 750 18 251 41, 500 37, 200 37, 250 35, 720 37, 734 40, 012	1, 158 1, 573 1, 280 990 1, 690 1, 285 1, 120 2, 280 2, 005 2, 387 1, 973 2, 100 2, 434	11. 257 10, 250 22, 471 24, 100 16, 794 17, 733 23, 188 23, 720 26, 941 32, 690 29, 896 36, 014 35, 686 38, 446 45, 807	\$1, 373, 354 1, 353, 000 2, 273, 016 1, 948, 002 1, 084, 440 1, 562, 832 2, 136, 299 2, 205, 793 2, 811, 275 4, 550, 840 3, 078, 524 4, 3995, 119 6, 033, 133 8, 874, 711

<sup>&</sup>lt;sup>1</sup> No output of gold or copper was recorded in New York during this period.

There are no zinc or lead smelters in New York. The Phelps Dodge Refining Corporation has a custom copper smelter and an electrolytic refinery at Laurel Hill which treat copper ore, matte, bullion, and copper-bearing scrap material.

#### NORTH CAROLINA

Gold production in North Carolina increased 26 percent in 1942 over 1941, silver increased 11 percent, and copper decreased 10 percent. The increase in gold resulted from continuous operation from January to about October 15 of the Condor (old Howie) mine at Waxhaw in Union County, operated under lease by Hugh Jardine. This mine was reopened in 1940, and the ore produced in that year was shipped to the Capps cyanide mill at Charlotte for treatment. Operations during the first part of 1941 were confined to development work and the building of a 100-ton countercurrent cyanide mill on the property. The mill was placed in operation on July 15, 1941, and ran steadily until October 1942, when both mine and mill were closed in compliance with the Gold-Mining Limitation Order of the War Production Board. The total production in the 3 years was 42,018 tons of ore, yielding 8,967 fine ounces of gold and 6,073 fine ounces of silver valued in all (on the basis of mint returns) at \$318,187. Scattered small shippers of amalgam retorts and gold dust to the Philadelphia Mint and New York Assay Office during 1942 were: Wright Mines, Inc., in Franklin County; Passavant Bros., Enfield, Halifax County; Joe Rogers, near Indian Trail, and John L. James, Charlotte, both in Mecklenburg County; and C. F. Crisson, Nebo, McDowell County.

Copper output from the Fontana copper mine in Swain County decreased in 1942. The mine is operated by the North Carolina Exploration Co., which ships the crude ore to the Tennessee Copper Co. smelter at Copperhill, Tenn. The ore contains very small quantities of gold and silver, some of which are recovered as byproducts in refining the copper bullion. E. C. McSwain sank a 40-foot shaft at a prospect on his property in Chatham County near Hemp and shipped 33 tons of copper-silver ore to the U. S. Metals Refining Co. at Carteret, N. J., and 100 tons (wet weight) to the Daugherty Chemical Co., Troy, N. C. Diamond drilling was done on the old Silver Hill property in Davidson County, which has produced zinc-

lead ore containing copper, gold, and silver.

#### PENNSYLVANIA

The Bethlehem Steel Co. continued in 1942 to recover gold, silver, and copper as byproducts of iron mining at its Cornwall mine in Lebanon County, Pa. The mine is developed by an open pit and three inclined shafts, which had reached a depth of 1,700 feet at the end of the year. The ore minerals are magnetite, pyrite, and chalcopyrite (carrying a little gold and silver). The ore-treatment plants comprise a 6,500-ton magnetic separation plant producing iron concentrates, a 2,400-ton sintering plant for handling the iron concentrates, and a 2,800-ton flotation mill in which the tailings from the magnetic plant are concentrated to recover copper, gold, and silver. The quantity of each of these metals recovered was larger in 1942 than in 1941.

SOUTH CAROLINA

Although gold production in South Carolina declined 50 percent in 1942 from 1941, the State continued to rank first among the Eastern States in gold output. Operations at the old Haile mine

near Kershaw, which contributed the bulk of the State output from 1937 to 1942, inclusive, were suspended in September 1942, presumably for the duration of the war. The ore was mined chiefly from open pits and was treated in the 400-ton cyanide mill on the property. The total production from the mine in the 6-year period ended 1942 was 538,046 tons of ore yielding 60,013 fine ounces of gold and 27,048 fine ounces of silver having a total net value (based on mint returns) of \$2,115,079. Small tonnages of gold ore containing a little silver and copper were shipped to the U. S. Metals Refining Co. smelter at Carteret, N. J., by L. M. Martin of Kings Creek and E. R. Vreeland of Smyrna. W. K. Hunter shipped 214 tons of gold ore from Hickory Grove to the Tennessee Copper Co. smelter at Copperhill, Tenn.

#### TENNESSEE

Zinc production (in terms of recovered metal) in Tennessee in 1942 totaled 43,971 tons and exceeded the previous record annual output of 1941 by 7,801 tons. The output of recovered copper and lead also increased, but that of gold and silver decreased. The gold and silver and some of the zinc were byproducts of the copper-iron mining, milling, and smelting operations of the Tennessee Copper Co. at Ducktown and Copperhill in Polk County. Important commercial products derived from the copper-iron ores (besides copper bullion and zinc concentrates) included sulfuric acid and copper sulfate manufactured in the company plants and iron sinter sold to iron and steel producers, mostly in the Birmingham (Ala.) district. The zinc concentrates produced in the mills were sold to the Donora (Pa.) The copper-iron sulfide concentrates and direct-smelting crude ore were treated in the company Copperhill smelter, which also treated copper-iron sulfide ore from the Fontana mine in Swain County, N. C. The crude copper ore is treated in the reverberatory furnace, yielding matte which is sent to the converter. The concentrates are fed directly into the converter. Most of the blister copper from the converter is cast into pigs and shipped to an electrolytic refinery on the Atlantic seaboard, where the byproduct gold and silver are recovered. Shot copper is produced for use in the copper sulfate Two blast furnaces maintained as stand-by equipment are operated when the company desires to increase production of sulfuric In 1942 the company operated the Burra Burra, Eureka, and Boyd groups of mines and the London and Isabella selective flotation The rated daily capacity of the mills at the end of the year was 1,450 and 1,050 tons, respectively. The ore is hoisted through vertical shafts, one of which is 2,400 feet deep. Development done in 1942 totaled 383 feet of shaft, 17,307 feet of drifts, and 14,802 feet of diamond drilling.

From 1928 to 1939, inclusive, the Bureau of Mines was not at liberty to publish separate State totals for lead and zinc production in some of the Eastern States, and the figures for those States were combined under Tennessee in the chapters of this series. As separate State totals may now be published for Tennessee and Virginia, the totals for Tennessee from 1928 to 1942 are shown in the accompanying table. Figures for Virginia are given in the following review

for that State.

Mine production of lead and zinc in Tennessee, 1928-42, in short tons, in terms of recovered metals

Year	Ore 1 sold or treated	Lead	Zine 1	Year	Ore 1 sold or treated	Lead	Zinc 1
1928	570, 199 682, 680 709, 760 779, 500 631, 400 652, 820 828, 215 750, 440	13 215 430 296 340 190	14, 597 19, 805 22, 606 25, 320 12, 841 21, 442 25, 972 23, 102	1936 1937 1938 1938 1939 1940 1941	849, 833 987, 256 909, 700 1, 083, 900 1, 216, 044 1, 300, 916 1, 560, 259	805 405 553 517 573 23 238	23, 830 29, 335 29, 810 32, 375 34, 796 36, 170 43, 971

Ore figures exclude copper ore, from which some zinc was recovered as a byproduct each year from 1930 to 1942, inclusive. Such byproduct zinc is included in zinc figures.

Most of the zinc output of Tennessee in 1942, as in 1941, came from four mines in Knox and Jefferson Counties. Three of these—Mascot No. 2, Jarnagin, and Grasselli—were operated by the American Zinc Co. of Tennessee. The Mascot is opened by a 520-foot shaft and an inclined shaft from the 520-foot level to the maximum depth of 850 The Grasselli has one operating shaft and an auxiliary manway shaft and is 350 feet deep. The Jarnagin has one operating shaft 280 feet deep, with an auxiliary manway shaft. All the mines are fully mechanized, and slushing is the principal method of loading. velopment done at the three mines in 1942 totaled 5,419 feet of drifts, 8,516 feet of diamond drilling, and 25,877 feet of churn drilling. crude ore from all three mines was treated in the company mill at the Mascot No. 2 mine at Mascot. The ore from the Grasselli and Jarnagin—12 and 16 miles, respectively, east of Mascot—was transported to the mill over the Southern Railway. The mill is equipped with a differential-density cone unit, jigs, and flotation machines. It treated 1,263,039 tons of crude ore in 1942, and its total output of zinc concentrates was 55,831 tons—a 25-percent increase over 1941. The company planned to open a fourth mine—the newly developed Carson Newman (Athletic Field) at Jefferson City-in 1943; the ore will be shipped to the Mascot mill. The other large zinc producer in 1942 was the Davis property of the Universal Exploration Co. at Jefferson City, which is equipped with an 800-ton flotation mill for treating sulfide ore and a small plant for concentrating carbonate ore. The flotation mill was operated at near capacity throughout the year, and the carbonate plant treated a small tonnage daily. output of both sulfide and carbonate concentrates was larger than in The average grade of the blende shipped in 1942 was 64.53 percent zinc. The Embree Iron Co. produced several cars of zinc and lead carbonate concentrates monthly from April through December at its property near Embreeville, Washington County. In Claiborne County the Imperial Mining Co. operated the Bunche's Hollow mine 2 miles northwest of Goin during part of 1942; the mine is equipped with a small jig mill. Dr. Gant Gaither shipped 324 tons of 58-percent zinc concentrates from the Hoover mine 10 miles northeast of Murfreesboro; the ore was concentrated in a 4-cell jig. Blow shipped ore from a prospect on his property in Union County to the flotation mill at the Austinville (Va.) mine.

#### VERMONT

In August 1942 the Vermont Copper Co., Inc., entered into a contract with the Metals Reserve Co. to reopen and reequip the Elizabeth copper mine near South Strafford, Orange County, and operate it for 2½ years. The copper produced is to be sold to the Metals Reserve Co. Construction of a 500-ton concentration mill and reequipment of the mine was begun in October. The mine had not been worked since June 1930. The ore minerals are chalcopyrite and pyrrhotite, carrying some silver.

#### VIRGINIA

Gold mines operating in Virginia in 1942 were the Red Bank lode mine 5 miles north of Virgilina, Halifax County, equipped with a small amalgamation mill, and the Ruth placer mine on Byrd Creek in Goochland and Fluvanna Counties, equipped with a dragline and portable washing plant; each of the mines operated about 3 months, and their combined output was 99 ounces of gold and 32 ounces of silver. Some gold and silver were recovered from zinc-lead-iron-copper-silver-gold ore from the old Valzinco mine 6 miles southeast of Paytes post office, Spotsylvania County, which was reopened during the year by Panaminas, Inc., subsidiary of Ventures, Ltd. The company built a 100-ton selective flotation mill at the mine and began treating ore in September. The products of the mill were zinc concentrates, carrying lead, copper, silver, and gold; and lead concentrates, carrying copper, zinc, silver, and gold. Several hundred tons of the zinc concentrates were shipped to the American Zinc & Chemical Co. smelter at Langeloth, Pa., in 1942.

では、これのでは、100mのでは、100

The total output of recoverable lead in Virginia in 1942 was 1.803 tons and that of zinc 15,991 tons compared with 1,916 and 18,483 The foregoing 1941 figures for recoverable tons, respectively, in 1941. lead and zinc represent actual mine production during the year and are lower than those representing mine shipments given in Minerals Yearbook, 1941, which include 4,430 tons of zinc and 1,474 tons of lead contained in concentrates shipped from stocks accumulated before 1941 but not previously included in the annual production sta-The bulk of the State output of lead and zinc from 1928 through 1942 came from the Austinville mine in Wythe County. In 1942 the mine operated two shifts a day, 6 days a week. The ore was treated in the 2,000-ton selective flotation mill at the mine. After April the mill also handled small tonnages monthly of purchased The Lacy-Butler Co. shipped 708 tons of zinc carbonate ore to the smelters at Palmerton, Pa., and Meadowbrook, W. Va., from the leased Little Wythe mine at Cripple Creek, also in Wythe County.


The following table shows mine production of gold, silver, copper, lead, and zinc in Virginia, 1928–42; the Bureau of Mines has not been at liberty heretofore to show the annual figures for 1928 to 1939, inclusive.

# GOLD, SILVER, COPPER, LEAD, AND ZINC IN THE EASTERN STATES 361

Mine production of gold, silver, copper, lead, and zinc in Virginia, 1928-42, in terms of recovered metals

Year	Ore sold or treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (short tons)	Zinc (short tons)	Total value
1928 1929 1930 1931 1932 1933 1933 1933 1935 1936 1937 1938 1939 1940 1941	509, 217 501, 200 572, 540 502, 150 304, 773 247, 530 263, 144 318, 721 491, 830 587, 469 649, 436 653, 581 602, 239 502, 130	31 32 667 653 909 1,396 2,943 364 458 240 109	8 103 55 96 111 502 1,780 271 135 1,793	400 700 1,000 47,300	5, 824 6, 336 7, 196 6, 186 2, 750 1, 830 1, 595 3, 507 4, 070 2, 854 5, 338 3, 380 2, 225 3, 390 1, 803	18, 320 20, 753 25, 541 12, 992 5, 673 11, 328 21, 740 25, 730 21, 086 25, 920 26, 956 23, 850 16, 927 22, 913 115, 991	\$2, 910, 624 3, 537, 732 3, 171, 536 1, 445, 156 506, 019 1, 087, 796 2, 011, 084 2, 567, 738 3, 755, 442 3, 186, 837 3, 777, 525 3, 831, 906 5, 227, 673

<sup>1</sup> Actual production during year; figures for some of the earlier years represent mine shipments.



### GOLD, SILVER, COPPER, LEAD, AND ZINC IN IDAHO

(MINE REPORT)

By G. E. WOODWARD AND PAUL LUFF

#### SUMMARY OUTLINE

	Page		Page
Summary	363	Metallurgic industry	. 369
Calculation of value of metal production	363	Review by counties and districts	. 374
Mine production by counties	367	Coeur d'Alene region	. 382
Mining industry			
Ore classification	369		

#### SUMMARY

The total value of gold, silver, copper, lead, and zinc produced by Idaho mines was \$46,063,326 in 1942 compared with \$41,776,848 in 1941—a 10-percent increase (see fig. 1). The value of the gold output was \$3,325,700 (7 percent of the State total), silver \$10,414,144 (nearly 23 percent), copper \$830,060 (2 percent), lead \$15,263,806 (33 percent), and zinc \$16,229,616 (35 percent). Production of lead in Idaho in 1942 (227,818,000 pounds) was the largest since 1930, and the output of zinc (174,512,000 pounds) was by far the greatest in any year in the history of the State. Compared with 1941 the gold output decreased nearly 37 percent, silver 12 percent, and copper 5 percent; lead increased more than 8 percent and zinc 10 percent.

The production of copper, lead, and zinc in Idaho in 1942 was

The production of copper, lead, and zinc in Idaho in 1942 was affected by several factors. The Metals Reserve Co. announced that, effective February 1, 1942, premiums amounting to 5 cents a pound for copper and 2¾ cents a pound for both lead and zinc would be paid for these metals produced in excess of certain fixed basic quotas. The basic quota of each mine was fixed according to 1941 output; however, several zinc-lead producers in Idaho, particularly in the Coeur d'Alene region, could not maintain their 1941 production rate, and during the fall of 1942 lower basic production quotas were granted to certain companies. Also, effective December 1, 1942, the Metals Reserve Co. announced that it would pay an additional premium of 2¾ cents a pound for lead and two additional premiums of 2¾ cents a pound for zinc for overquota metal production.

A labor shortage began in April at the mines, mills, and smelters in Idaho, resulting from men leaving to take jobs on Government construction projects and in war industries where abnormally high wages were paid. This shortage became so acute during the summer that some mines closed and others curtailed output 50 percent. The seriousness of the condition was recognized by the War Department, which furloughed about 800 soldiers in October for service in Idaho mines. This action tended to relieve the shortage but did not insure

an adequate labor supply.

All tonnage figures are short tons and "dry weight"; that is, they

do not include moisture.

The value of metal production herein reported has been calculated at the following prices.

363

### Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zine 4
1938	Per fine ounce \$35.00 35.00 35.00 35.00 35.00	Per fine ounce \$ \$0.646+ \$ .678+ 7 .711+ 7 .711+ 7 .711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057 .067	Per pound \$0.048 .052 .063 .075

¹ Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from Jan. 18, 1837, to Jan, 31, 1934, was \$20.67+(\$20.671835) per fine ounce.
² Treasury buying price for newly mined silver.
² 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.
² 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.
² \$0.64646464.

Mine production of gold, silver, copper, lead, and zinc in Idaho, 1938-42, and total, 1863-1942, in terms of recovered metals

	Mines p	roducing		Gold (lode	and placer)	Silver (lod	e and placer)
Year	Lode	Placer	Ore (short tons)	Fine ounces	Value	Fine ounces	Value
1938	305 362 378 331 203	463 465 548 524 236	1, 999, 147 2, 108, 445 2, 556, 687 2, 704, 680 2, 900, 704	103, 513 116, 662 146, 480 149, 816 95, 020	\$3, 622, 955 4, 083, 170 5, 126, 800 5, 243, 560 3, 325, 700	18, 993, 676 17, 222, 370 17, 552, 240 16, 672, 410 14, 644, 890	\$12, 278, 740 11, 690, 336 12, 481, 593 11, 855, 936 10, 414, 144
1863-1942			(1)	7,724,178	173, 485, 633	484, 219, 847	332, 614, 231
	Cop	oper	Le	ead	Z		
Year	Pounds	Value	Pounds	Value	Pounds	Value	Total value
1938 1939 1940 1941 1942	4, 278, 000 5, 032, 000 6, 698, 000 7, 242, 000 6, 860, 000	\$419, 244 523, 328 756, 874 854, 556 830, 060	184, 354, 000 181, 962, 000 209, 668, 000 209, 828, 000 227, 818, 000	\$8, 480, 284 8, 552, 214 10, 483, 400 11, 960, 196 15, 263, 806	88, 060, 000 95, 098, 000 141, 202, 000 158, 168, 000 174, 512, 000	\$4, 226, 880 4, 945, 096 8, 895, 726 11, 862, 600 16, 229, 616	\$29, 028, 103 29, 794, 144 37, 744, 393 41, 776, 848 46, 063, 326
1863-1942	<b>2</b> 101, 189	31, 142, 807	<sup>2</sup> 5, 631, 963	603, 194, 868	<sup>2</sup> 960, 623	135, 022, 899	1, 275, 460, 438

<sup>1</sup> Figures not available.

#### Gold and silver produced at placer mines in Idaho, 1938-42, in fine ounces, in terms of recovered metals

	Clusion	a ond					D	redges				•
Year	hydi	ng and aulic	Drift:	mining	Dry-l	and 1	Dragline Floating bucket				То	tal
	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver
1938 1939 1940 1941 1942	4, 987 5, 443 6, 664 4, 899 1, 197	969 1, 638 1, 337 1, 149 234	410 196 291 228 83	57 26 48 46 7	1, 989 4, 475 5, 623 3, 185 563	384 1,332 758 388 60	15, 459 9, 576 6, 569 11, 725 6, 126	5, 818 4, 389 5, 427 2, 100 879	31, 234 28, 973 41, 262 52, 358 36, 611	10, 100 7, 490 10, 226 13, 725 9, 291	54, 079 48, 663 60, 409 72, 395 44, 580	17, 328 14, 875 17, 796 17, 408 10, 471

<sup>&</sup>lt;sup>1</sup> A floating washing plant supplied with gravel by a dragline excavator is called a "dragline floating dredge"; a stationary or movable washing plant supplied with gravel by any type of power excavator is called a "dry-land dredge."

<sup>2</sup> Short tons.

Gold.—The output of recoverable gold in Idaho was nearly 37 percent less in 1942 than in 1941. This decrease is attributed in part to the gold-mine closing order issued by the Government in October; but several large gold producers, both lode and placer, had shut down before the closing order was issued, owing to difficulty of obtaining labor and supplies. The yield of gold from lode mines decreased 35 percent and that from placers 38 percent. About 37 percent of the State total gold in 1942 came from siliceous gold ore and more than 45 percent from all types of dredging operations. Ten floating (bucket) dredges, 2 less than in 1941, treated 7,772,947 cubic yards of gravel and recovered 36,611 ounces of gold—a decrease of 15,747 ounces from 1941; 7 dragline dredges and 5 dry-land dredges treated 1,175,937 cubic yards of gravel and recovered 6,689 ounces of golda decrease of 8,221 ounces. Of the total placer gold, 91 percent came from the Boise Basin, Elk City, Gibbonsville, Hoodoo, Middle Boise, and Yankee Fork districts, where dredges were operated. Nearly half of the total lode gold came from the Middle Boise (Atlanta) Large decreases in output of gold were made in the Elk City, Boise Basin, Yellow Pine, Yankee Fork, Warren, and Burgdorf-Marshall Lake districts.




FIGURE 1.—Value of mine production of gold, silver, lead, and zinc and total value of gold, silver, copper, lead, and zinc in Idaho, 1870-1942. The value of copper has been less than \$2,000,000 annually, except in a few years.

Talache Mines, Inc., operating a lode property at Atlanta, was by far the largest gold producer in Idaho. It was followed by the Fisher-Baumhoff Co., operating two bucket dredges near Centerville; Boise King Placers, operating a bucket dredge near Twin Springs; Northwest Goldfields bucket dredge near Harvard; Idaho-Canadian Dredging Co. bucket dredge at Idaho City; Snake River Mining Co., operating a bucket dredge at Sunbeam; Triumph lode mine near Ketchum; and De Lamar Milling Corporation at De Lamar.

Silver.—The output of recoverable silver in Idaho was 14,644,890 fine ounces in 1942—a 12-percent decrease from 1941. Production from the Sunshine mine, largest silver producer in the United States, declined more than 2,000,000 ounces. The Coeur d'Alene region produced nearly 89 percent of the State total silver in 1942; the rest came largely from the Warm Springs, Carson, Bayhorse, South

Mountain, Yellow Pine, and Middle Boise districts. Silver ore yielded 51 percent of the State total silver, zinc-lead ore 37 percent, lead ore 8 percent, and gold-silver ore and gold ore 3 percent. The yield of silver from silver ore decreased 2,340,416 ounces, but that from zinc-lead ore increased 404,842 ounces and from lead ore 60,433 ounces.

Eight mines—the Sunshine, Bunker Hill & Sullivan, Mineral Point, Hecla, Polaris, Triumph, Morning, and Page—produced 81 percent of the silver output of the State during 1942. All these mines

except the Triumph are in the Coeur d'Alene region.

Copper.—The output of recoverable copper in Idaho in 1942 was 6,860,000 pounds—a 5-percent decrease from 1941. The loss resulted mainly from decreased output of silver-copper ore and copper ore. Silver ore (chiefly from mines in the Coeur d'Alene region) yielded 69 percent of the State total copper, zinc-lead ore 23 percent, copper ore 3 percent, zinc ore 3 percent, and lead ore 2 percent.

The Mineral Point and Sunshine mines produced 64 percent of the

total copper output of the State in 1942.

Lead.—The output of recoverable lead in Idaho was 227,818,000 pounds in 1942—an increase of more than 8 percent over 1941. Marked increases in lead output at the Hecla, Page, Sherman, Bunker Hill & Sullivan, Dayrock, and Star properties more than offset large decreases at the Morning and Triumph mines. About 93 percent of the State total lead came from the Coeur d'Alene region; most of the remainder was produced in the Warm Springs, Bayhorse, Port Hill, and Pend d'Oreille districts. Zinc-lead ore and old tailings from the Coeur d'Alene region yielded 81 percent of the State total lead; and lead ore, chiefly from the Coeur d'Alene region, yielded 14 percent. Lead recovered from zinc-lead ore increased 13,185,657 pounds and from lead ore 4,824,358 pounds.

In 1942 the combined lead output of the three largest producers—the Bunker Hill & Sullivan, Hecla, and Morning—was 131,219,137 pounds (127,137,585 pounds in 1941), or more than 57 percent of the State total; other important producers were the Page, Star, Sherman, Tamarack, Triumph, Dayrock, Clayton, and Gold Hunter properties.

Zinc.—The output of recoverable zinc in Idaho was 174,512,000 pounds in 1942—a 10-percent increase over the former record output (1941). The gain was due principally to increased output of zinc from mines in the Coeur d'Alene region, especially from the Hecla, Star, Page, Tamarack, and Spokane-Idaho properties; however, a substantial decrease was reported from the Bunker Hill & Sullivan mine. Nearly 90 percent of the State total zinc in 1942 came from the Coeur d'Alene region and nearly all the remainder from the Warm Springs, South Mountain, Bayhorse, Deadwood Basin, and Alder Creek districts. Zinc-lead ore and old tailings concentrated yielded 97 percent of the State total zinc, and zinc ore concentrated most of the remainder.

Seven mines—the Star, Morning, Hecla, Bunker Hill & Sullivan, Tamarack, Triumph, and Page—produced 82 percent of the State

total zinc in 1942.

## MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in Idaho in 1942, by counties, in terms of recovered metals

· * * * * * * * * * * * * * * * * * * *		Mines p	oducing	Gold (lode	and placer)	Silver (lode	and placer)
County		Lode	Placer	Fine ounces	Value	Fine ounces	Value
AdaAdams		1 4	4	516 16	\$18,060 560 490	152 547	\$100 389
Benewah Blaine		25	2	5, 059	177, 065	652, 590	464, 06
Boise		15	38	14, 731	515, 585	37,052	26, 34
Bonner		4	······································	3 33	105 1, 155	54,699	38, 89
Bonneville Boundary		<u>1</u>		11	385	39, 673	28, 21 1, 10
Butte		4	<u>2</u>	2	70	1,551 8,827	1, 10
Camas Clark		4	2	<b>2</b> 65	9, 275	66	6, 27 4
Clearwater			12	22	770	7	
Custer Elmore		19 9	5 15	6, 190 29, 576	216, 650 1, 035, 160	215,003	152, 89 68, 89
Jem		3	2	2,917	102,095	96, 878 21, 496	15, 28
[daho		29	69	12,774	447,090	8, 280	5, 88
ferome Kootenai		ī	12	38	1, 330	14	1
Latah			4	6,021	210, 735	329	23
Lemhi		17	32 2	6,843 2	239, 505 70	42, 200	30, 00
Lewis Nez Perce			1	3	105		
Owyhee Shoshone Cwin Falls		10	8 7	3, 548	124, 180	329,071	234, 00
Shoshone Dwin Falls		49	13	2, 688 37	94, 080 1, 295	12, 977, 287	9, 228, 29
Valley		5	5 1	3, 708	1, 295 129, 780	152, 380 6, 781	108, 35
Washington		2	1	3	105	6, 781	4, 82
			000	95, 020	3, 325, 700	14, 644, 890	10, 414, 14
Гotal, 1941		203 331	236 524	149, 816	3, 325, 700 5, 243, 560	16, 672, 410	11, 855, 93
	Сор	331	524	149, 816		ne	11, 855, 93
County		331	524	149, 816		16, 672, 410	11, 855, 93
,	Cop	331 per	524	149, 816	Zi	ne	11, 855, 93 Total valu
County	Cop	per Value	524	149, 816	Zi	ne	11, 855, 93  Total valu
County  AdaAdams	Cop Pounds 35, 900	331 per	Le Pounds	value	Pounds	16, 672, 410  ne  Value	11, 855, 93  Total valu  \$18, 16 5, 29 49
County  AdaAdamsBlaine	Cop Pounds 35, 900 340, 000	331  per  Value  \$4,344  41,140	Le Pounds	value	Zi	ne	11, 855, 98  Total valu  \$18, 16  5, 28
County  Ada Adams Benewah Blaine Boise	Cop Pounds 35, 900 340, 000	331  per  Value  \$4,344  41,140  254	Founds 7, 646, 400 25, 000	Value \$512, 309	Pounds	16, 672, 410  ne  Value	11, 855, 98  Total valu  \$18, 16  5, 26  2, 365, 77  543, 98  91, 56
County  Ada	Cop Pounds  35, 900  340, 000 2, 100 2, 200	\$4,344 41,140 254 266	Founds  7, 646, 400 25, 000 780, 600	Value  \$512, 309 1, 675 52, 300	Pounds	16, 672, 410  ne  Value	11, 855, 98  Total valu  \$18, 16  5, 22  2, 365, 72  543, 86  91, 56  1, 18
County  Ada Adams	Cop Pounds 35, 900 340, 000	331  per  Value  \$4,344  41,140  254	Founds	Value  \$512, 309 1, 675 52, 300 139, 896	Pounds	Value \$\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\	11, 855, 93  Total valu  \$18, 16  5, 26  2, 365, 75  643, 91, 56  1, 18
County  Ada Adams Benewah Blaine Boise Boonner Bonneville Boundary	Cop Pounds  35, 900  340,000 2, 100 2, 200 16,000	\$4,344 41,140 254 266	Founds	\$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025	Pounds	16, 672, 410  ne  Value	11, 855, 93  Total value  \$18, 16  5, 29  49  2, 365, 72  543, 86  91, 56  1, 11  170, 42  8, 44  16, 66
County  Ada	Cop Pounds  35, 900  340, 000 2, 100 2, 200	331  Per Value  \$4,344  41,140 254 266  1,936	Founds  7, 646, 400 25, 000 780, 600	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717	Pounds	Value \$1,171,149 2,576	11, 855, 93  Total value  \$18, 16 5, 22 2, 365, 77 543, 89 1, 56 1, 14 170, 44 16, 66 93
County  Ada	Cop. Pounds  35, 900  340, 000 2, 100 2, 200  16, 000  700	331  Per  Value  \$4,344  41,140 254 266  1,936	524  Pounds  7, 646, 400 25, 000 780, 600  2, 088, 000 70, 400 15, 300 13, 300	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891	Pounds  12, 593, 000  27, 700 300	Value	11, 855, 93  Total value  \$18, 16 5, 26 44 2, 365, 77 543, 86 91, 56 1, 11 170, 44 8, 44 16, 66
County  Ada	Cop Pounds  35,900  340,000 2,100 2,200  16,000  700	331  Per  Value  \$4,344  41,140 254 266  1,936  85  18,876	7, 646, 400 25, 000 780, 600 15, 300 13, 300 3, 317, 000	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239	Pounds	Value  \$1, 171, 149  2, 576 28  149, 544	11, 855, 93  Total valu  \$18, 16 5, 29 2, 365, 72 543, 86 91, 56 1, 11 170, 42 16, 66 93 77 760, 22 1, 104, 04
County  Ada	Cop Pounds  35,900  340,000 2,100 2,200  16,000  700  156,000  11,000	\$4,344 41,140 254 266 1,936 18,876	7, 646, 400 25, 000 780, 600 2, 088, 000 70, 400 13, 300 3, 317, 000	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239 6, 077	Pounds  12, 593, 000  27, 700 300	Value	11, 855, 93  Total valu  \$18, 16     5, 23     44     2, 365, 77     543, 86     91, 56     1, 11     170, 44     8, 44     16, 66     97     760, 22     1, 104, 00     125, 22
County  Ada. Adams. Benewah Blaine. Boise. Bonneville. Boundary. Butte. Damas. Dlark. Clearwater. Uster. Elmore. Jem. ddaho.	Cop Pounds  35,900  340,000 2,100 2,200  16,000  700	331  Per Value  \$4,344  41,140 254 266  1,936  85  18,876	7, 646, 400 25, 000 780, 600 15, 300 13, 300 3, 317, 000	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239	Pounds	Value  \$1, 171, 149  2, 576 28  149, 544	\$11, 855, 93  Total value  \$18, 16 5, 26 47 543, 86 91, 19 170, 44 16, 66 77 760, 20 1, 104, 00 125, 22 453, 51
County  Ada	Cop Pounds  35,900  340,000 2,100 2,200  16,000  700  156,000  11,000	\$4,344 41,140 254 266 1,936 18,876	7, 646, 400 25, 000 780, 600 2, 088, 000 70, 400 13, 300 3, 317, 000	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239 6, 077	Pounds	Value  \$1, 171, 149  2, 576 28  149, 544	11, 855, 93  Total valu  \$18, 16 5, 26 2, 365, 72 543, 86 91, 56 1, 16 170, 48 16, 66 92 77 760, 22 1, 104, 06 125, 22 453, 57 1, 3
County  Ada	Cop Pounds  35,900  340,000 2,100 2,200  16,000  700  156,000  11,000 3,100	331  Per  Value  \$4,344  41,140 254 266  1,936  85  18,876  1,331 375	7, 646, 400 25, 000 780, 600 15, 300 13, 300 3, 317, 000 90, 700 2, 400	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239 6, 077 161 60	Pounds  12, 593, 000  27, 700 300  1, 608, 000	Value  \$1, 171, 149  2, 576 28  149, 544	11, 855, 93  Total valu  \$18, 16 5, 29 2, 365, 72 543, 86 91, 56 1, 11 170, 42 8, 44 16, 66 93 77 760, 22 1, 104, 01 125, 22 453, 51 1, 3
County  Ada	Cop Pounds  35,900  340,000 2,100 2,200  16,000  700  156,000  11,000	\$4,344 41,140 254 266 1,936 18,876	7, 646, 400 25, 000 780, 600 2, 88, 000 15, 300 13, 300 3, 317, 000 90, 700 2, 400	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239 6, 077 161	Pounds	Value  \$1, 171, 149  2, 576 28  149, 544	11, 855, 93  Total valu  \$18, 16 5, 29 2, 365, 72 543, 86 1, 18 170, 42 16, 66 93 77 760, 20 1, 104, 00 125, 22 453, 55 210, 96 314, 77
County  Ada Adams Benewah Blaine Boise Bonner Bonneville Boundary Butte Camas Clearwater Custer Elmore Adaho Gerome Kootenai Leatah Lemhi Lewhis Nez Perce	Cop Pounds  35, 900  340, 000 2, 100 2, 200  16, 000  156, 000  11, 000 3, 100  73, 000	\$4,344 \$4,344 41,140 254 266 1,936 18,876 1,331 375	7, 646, 400 25, 000 70, 400 13, 300 3, 317, 000 90, 700 2, 400	149, 816  Value  \$512, 309 1, 676 52, 300 139, 896 4, 717 1, 025 891  2222, 239 6, 077 161 60 29, 748	Pounds  12, 593, 000  27, 700  1, 608, 000  72, 000	16, 672, 410  Nalue  \$1, 171, 149  2, 576 28  149, 544  465  6, 696	11, 855, 93  Total valu  \$18, 16
County  Ada Adams Benewah Blaine Boise Bonner Bonner Bonner Camas Clark Clark Clearwater Cluster Elmore jem ddaho erome Kootenai Latah Lemhi Lemhi Lewis Nez Perce Dvyhee	73,000	\$4,344  41,140 254 266 1,936  85  18,876  1,331 375  8,833	7, 646, 400 25, 000 70, 400 13, 300 3, 317, 000 90, 700 2, 400	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239 6, 077 161 60 29, 748 8, 355	27, 700 27, 700 1, 608, 000 5, 000	Value  \$1,171,149  2,576 28  149,544  465  6,696	11, 855, 93  Total value  \$18, 16 5, 22 2, 365, 72 543, 89 1, 56 1, 11 170, 44 16, 66 125, 22 1, 104, 06 125, 22 453, 55 1, 33 210, 96 314, 77 6666, 11
County  Ada Adams Benewah Blaine Boise Bonneville Boundary Butte Camas Clearwater Custer Cleimore Cam County Count	73, 000  193, 200 5, 986, 000	\$4,344  41,140 254 266 1,936  85  18,876  18,876  23,377 724,306	7, 646, 400 25, 000 70, 400 15, 300 3, 317, 000 90, 700 2, 400 124, 400 212, 947, 000	149, 816  Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239 6, 077 161 60 29, 748 8, 355 14, 267, 449	2i Pounds  12, 593, 000  27, 700 300  1, 608, 000  5, 000  72, 000  2, 970, 000 156, 625, 000	Value  \$1, 171, 149  2, 576 28  149, 544  465  276, 210 14, 566, 125	11, 855, 93  Total valu  \$18, 16     5, 24  2, 365, 75     543, 86     91, 86     16, 66     125, 22     453, 53     1, 11     21, 104, 00     125, 22     453, 53     1, 33     210, 93     314, 77     666, 12     38, 860, 12
County  Ada Ada Adams Benewah Blaine Boise Bonneville Boundary Butte Camas Clark Clearwater Custer Elmore Jem Gaho erome Kootenai Letah Lemhi Lewis Nez Perce Owyhee Shoshone Twin Falls	Cop Pounds  35, 900  340,000 2, 100 2, 200  16, 000  156, 000  11, 000 3, 100  73, 000  193, 200 5, 986, 000  26, 000	\$4,344  41,140 254 266 1,936  85  18,876  18,876  23,377 724,306	7, 646, 400 25, 000 70, 400 15, 300 3, 317, 000 90, 700 2, 400 124, 400 212, 947, 000	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239 6, 077 161 60 29, 748	27, 700 27, 700 1, 608, 000 5, 000	Value  \$1,171,149  2,576 28  149,544  465  6,696	11, 855, 93  Total valu  \$18, 16 5, 29 2, 365, 72 543, 86 1, 18 170, 42 8, 44 16, 66 125, 25 210, 96 314, 77 210, 96 314, 73 314, 73 314, 73 314, 73 314, 73
County  Ada	73, 000  193, 200 5, 986, 000	\$4,344  41,140 254 266 1,936  85  18,876  1,331 375  8,833	7, 646, 400 25, 000 70, 400 13, 300 3, 317, 000 90, 700 2, 400	149, 816  Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239 6, 077 161 60 29, 748 8, 355 14, 267, 449	2i Pounds  12, 593, 000  27, 700 300  1, 608, 000  5, 000  72, 000  2, 970, 000 156, 625, 000	Value  \$1, 171, 149  2, 576 28  149, 544  465  276, 210 14, 566, 125	11, 855, 93  Total valu  \$18, 16 5, 29
County  Ada Ada Adams Benewah Blaine Boise Bonneville Boundary Butte Camas Clark Clearwater Custer Elmore Jem Gaho erome Kootenai Letah Lemhi Lewis Nez Perce Owyhee Shoshone Twin Falls	Cop Pounds  35, 900  340,000 2, 100 2, 200  16, 000  156, 000  11, 000 3, 100  73, 000  193, 200 5, 986, 000  26, 000	\$4,344  41,140 254 266 1,936  85  18,876  18,876  23,377 724,306	7, 646, 400 25, 000 70, 400 15, 300 3, 317, 000 90, 700 2, 400 124, 400 212, 947, 000	Value  \$512, 309 1, 675 52, 300 139, 896 4, 717 1, 025 891 222, 239 6, 077 161 60 29, 748	2i Pounds  12, 593, 000  27, 700 300  1, 608, 000  5, 000  72, 000  2, 970, 000 156, 625, 000	Value  \$1, 171, 149  2, 576 28  149, 544  465  276, 210 14, 566, 125	11, 855, 93  Total valu  \$18, 16 5, 29 2, 365, 72 543, 86 1, 18 170, 42 8, 44 16, 66 125, 25 210, 96 314, 77 210, 96 314, 73 314, 73 314, 73 314, 73 314, 73

Gold and silver produced at lode mines in Idaho in 1942, by counties, in terms of recovered metals

County	Ore sold or treated	Gold	Silver	County	Ore sold or treated	Gold	Silver
Ada Adams Blaine Boise Bonner Boundary Butte Camas Clark Custer Elmore	Short tons 40 89 114, 938 1, 473 12, 092 41, 353 1, 759 404 47, 961 87, 989	Fine ounces 20 16 5,059 1,597 3 11 2 263 1,397 23,166	Fine ounces 121 547 652, 590 33, 795 54, 699 39, 673 1, 551 8, 827 66 212, 587 94, 718	Gem	Short tons 6, 843 12, 053 2 48, 307 83, 522 2, 327, 417 114, 128 310 2, 900, 704 2, 704, 680		Fine ounces 21, 496 6, 421 14 864 329, 040 12, 977, 280 6, 781 14, 634, 419 16, 655, 002

Gold and silver produced at placer mines in Idaho in 1942, by counties, in fine ounces, in terms of recovered metals

			1	, , , , , ,	1							
	Cluic	ing and	Dwiff	t min-			D	redges				
County		raulic		ing		Dry-land 1		gline ing 1	Floatin	g bucket	Total	
	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver
Ada Benewah	4 14				492	31					496 14	31
Boise Bonneville Camas	389 33 2	78					79	23	12,666	3, 156	13, 134 33	3, 257
Clearwater Custer	17	4 4			5	3			4, 787	2,412	22 4, 793	7 2,416
Elmore Gem Idaho	64 8 346	11 73	15		61	11	3, 581	653	6, 346 4, 904	2, 149 1, 122	6, 410 8 8, 907	2, 160
Jerome Latah Lemhi	38 13 144	10	21						6,008	329	38 6, 021	1,859
Lewis Nez Perce	2 3						2, 466	203	1,900	123	4, 531 2 3	336
Owyhee Shoshone Twin Falls	13 15 37	16 7	47	7	5 	15 					18 62 37	31 7
Valley Washington	48 1	31									48	31
Total, 1941	1, 197 4, 899	234 1, 149	83 228	7 46	<sup>2</sup> 563 3, 185	<sup>2</sup> 60 388	<sup>3</sup> 6, 126 11, 725	<sup>3</sup> 879 2, 100	<sup>4</sup> 36, 611 52, 358	4 9, 291 13, 725	44, 580 72, 395	10, 471 17, 408

<sup>1</sup> A floating washing plant supplied with gravel by a dragline excavator is called a "dragline floating dredge"; a stationary or movable washing plant supplied with gravel by any type of power excavator is called a "dry-land dredge."

2 Recovered from 75,362 cubic yards of gravel treated by 5 dry-land dredges.

3 Recovered from 1,100,575 cubic yards of gravel treated by 7 dragline floating dredges.

4 Recovered from 7,772,947 cubic yards of gravel treated by 10 floating bucket dredges.

#### MINING INDUSTRY

The marked increase in output of lead, zinc, antimony, and tungsten, the closing of gold properties in October by Government order, and the serious shortage of labor at mines, mills, and smelters in the Coeur d'Alene region during the summer were the most important features of the mining industry of Idaho during 1942. The production of zinc, antimony, and tungsten was greater than in any year in the history of the State, and the output of lead was the largest since 1930. Zinc-lead ore (by far the chief output of the State) increased 15 percent over 1941 and lead ore nearly 48 percent; gold ore and gold-silver ore combined declined 23 percent, silver ore more than 6 percent, copper ore 72 percent, and zinc ore 9 percent.

#### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

Ore sold or treated in Idaho in 1942, with content in terms of recovered metals

Source	Mines produc- ing	Ore	Gold	Silver	Copper,	Lead	Zine
Dry and siliceous gold ore Dry and siliceous gold-silver ore Dry and siliceous silver ore	88 7 18	173, 389	7, 494	358, 263		60, 526	
Copper ore	1 112 8 40 1 8 52	2, 210	153 313 222	27, 390 1, 103, 683 12, 354 127, 670	190, 653 153, 272 7, 262	8, 090 31, 978, 714 36, 515 261, 057	132, 762
Total, lode mines Total, placers	1 203 236	2, 900, 704	50, 440 44, 580	14, 634, 419 10, 471	6, 860, 000	227, 818, 000	174, 512, 000
Total, 1941		2, 900, 704 2, 704, 680		14, 644, 890 16, 672, 410	6, 860, 000 7, 242, 000		174, 512, 000 158, 168, 000

<sup>1</sup> A mine producing more than 1 class of ore is counted but once in arriving at total for all classes.

#### METALLURGIC INDUSTRY

Of the 2,900,704 tons of ore produced in 1942 in Idaho, 2,762,323 tons (95 percent) were treated at concentration plants, 111,772 tons (4 percent) were treated at amalgamation and cyanidation mills, and 26,609 tons (1 percent) were shipped crude to smelters.

Ore treated at concentration plants in 1942 comprised 32,138 tons of gold ore, 168,913 tons of gold-silver ore, 447,130 tons of silver ore, 560 tons of copper ore, 306,083 tons of lead ore, 17,906 tons of zinc

ore, and 1,789,593 tons of zinc-lead ore.

Ore treated at straight amalgamation mills in 1942 totaled 11,402 tons, and ore treated at combined amalgamation and concentration plants comprised 97,670 tons. Ore treated at straight cyanidation plants in 1942 totaled 700 tons, and ore treated at combined cyanidation and concentration plants comprised 2,000 tons.

The lead smelter and refinery and the antimony plant of the Bunker Hill & Sullivan Mining & Concentrating Co. at Bradley were operated at capacity in 1942 on ore and concentrates, chiefly from mines and mills in the Coeur d'Alene region. The 100-ton electrolytic zinc plant of the Sullivan Mining Co. near Bradley operated at capacity on

concentrates from the same source.

In April 1943, the Bunker Hill & Sullivan Mining & Concentrating Co. completed its zinc-fuming plant at Bradley. According to a report by P. C. Fedderson, smelter superintendent at the Bunker Hill lead smelter, the operation will follow closely that practiced for some years by the Anaconda Copper Mining Co. at East Helena, Mont. The plant will treat all current hot slag and in addition cold reclaimed dump slag; it is expected to handle approximately 400 tons of slag a day, and this will produce about 50 tons of oxide fume containing 30 to 35 tons of zinc and about 5 tons of lead. That portion of the existing slag dump which can be re-treated economically for zinc recovery

contains about 1,000,000 tons, with an average zinc content of 10 percent. In September 1942 the Sunshine Mining Co. completed an electrolytic antimony plant (100-ton capacity) adjoining its concentration mill near Kellogg to recover antimony from silver-copperantimony concentrates.

Mine production of metals in Idaho in 1942, by methods of recovery, in terms of recovered metals

Method of recovery	Material treated	Gold	Silver	Copper	Lead	Zinc
Ore amalgamated Ore cyanided Concentrates smelted Ore smelted Placer	Short tons 109, 072 2, 700 406, 954 26, 609	Fine ounces 16, 580 391 30, 649 2, 820 44, 580	Fine ounces 8, 531 3, 304 14, 319, 082 303, 502 10, 471	Pounds 6, 636, 794 223, 206	Pounds  221, 566, 560 6, 251, 440	Pounds
Total, 1941		95, 020 149, 816	14, 644, 890 16, 672, 410	6, 860, 000 7, 242, 000	227, 818, 000 209, 828, 000	174, 512, 000 158, 168, 000

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in Idaho in 1942, by types of mills and by counties, in terms of recovered metals

#### AMALGAMATION MILLS

	7.5-1	Recove	ered in lion	Conc	entrates sn	nelted and	recovered 1	netal
County	Material treated	Gold	Silver	Concen- trates produced	Gold	Silver	Copper	Lead
AdaBoise	Short tons 40	Fine ounces 10 663	Fine ounces	Short tons 2	Fine ounces 10 10	Fine ounces 120 2	Pounds	Pounds
Custer Elmore Idaho Lemhi	1, 139 3, 230 87, 784 6, 604 541	292 12, 676 1, 874 85	502 6, 466 650 13	38 1,552 82	419 10, 416 934	12, 404 88, 167 4, 238	1,300	400
Owyhee Valley	9, 500	37 943	32 609	9	37	170		
Total, 1941	109, 072 173, 321	16, 580 20, 874	8, 531 12, 883	1, 685 2, 570	11, 826 18, 065	105, 101 167, 010	1, 300 8, 500	400 3, 300
		CY	ANIDAT	ION MIL	LS		<u>'                                    </u>	
CusterIdahoLemhi	2,000 220 480	297 44 50	3, 023 257 24	11	9	23		700
Total, 1941	2, 700 6, 182	391 659	3, 304 1, 486	11	9	23		700
Grand total: 1942 1941	111, 772 179, 503	16, 971 21, 533	11, 835 14, 369	1, 696 2, 570	11, 835 18, 065	105, 124 167, 010	1, 300 8, 500	1, 100 3, 300

Mine production of metals from concentrating mills in Idaho in 1942, by counties, in terms of recovered metals

		Concentrates smelted and recovered metal											
County	Ore treated	Concen- trates produced	Gold	Silver	Copper	Lead	Zinc						
Blaine Bonner Bonner Boundary Butte Camas Custer Elmore Gem Idaho Lemhi Owyhee Shoshone Valley Total, 1941	Short tons 111, 111 12, 020 41, 353 1, 759 5 38, 638 200 6, 791 5, 168 45, 900 83, 253 2, 311, 531 104, 594 2, 762, 323 2, 492, 644	Short tons 28, 949 630 1, 541 113 2 2 3, 570 7 2, 122 1, 065 3, 700 354, 290 9, 210 405, 258 350, 802	Fine ounces 4, 219 2 11 2 53 36 2, 906 879 2, 050 3, 377 2, 579 2, 700 18, 814 33, 331	Fine ounces 637, 273 47, 072 39, 673 1, 551 141, 173 57 21, 421 1, 129 33, 113 327, 687 12, 819, 649 144, 059 14, 213, 958 15, 924, 836	Pounds 332, 115 1, 600 16, 000 24, 544 10, 868 1, 200 68, 200 193, 200 5, 961, 767 26, 000 6, 635, 494 6, 619, 249	Pounds 7, 553, 263 713, 712 2, 088, 000 70, 400 70, 400 1, 600 89, 400 124, 700 207, 611, 671 221, 565, 460 2201, 793, 685	Pounds 12,585,705 27,700 1,095,000 5,000 2,970,000 156,515,672 611,000 173,810,377 158,030,326						

Gross metal content of concentrates produced from ores mined in Idaho in 1942, by classes of concentrates smelted

Olomos announted	Concen-		Gr	oss metal cor	ntent		
Class of concentrates	trates produced	Gold	Silver	Copper	Lead	Zinc	
Dry gold Dry gold-silver	Short tons 5, 018 7, 876	Fine ounces 18, 341 5, 092	Fine ounces 121, 707 314, 016	Pounds 16, 693	Pounds 110, 458	Pounds	
Dry silver Copper Lead	8, 091 184, 158	1 164 2, 597	332 6, 374, 672 5, 554, 027	4, 719, 226 1, 177, 017	215, 338 214, 906, 445	21, 755, 33	
Lead-copper Zine Zine-lead Dry iron (from zine-lead ore)_	2, 686 145, 601 38, 009 15, 514	323 1, 284 331 2, 516	960, 127 501, 547 191, 310 301, 344	508, 500 591, 196 126, 513 231, 838	643, 104 7, 861, 236 6, 540, 421 388, 467	265, 66 155, 098, 72 38, 099, 51 712, 57	
Total, 1941	406, 954 353, 372	30, 649 51, 396	14, 319, 082 16, 091, 846	7, 370, 983 7, 496, 404	230, 665, 469 210, 025, 930	215, 931, 81 192, 921, 20	

Mine production of metals from Idaho concentrates shipped to smelters in 1942, in terms of recovered metals

#### BY COUNTIES

	Concen- trates	Gold	Silver	Copper	Lead	Zinc
Ada	Short tons	Fine ounces	Fine ounces	Pounds	Pounds	Pounds
BlaineBoise	28, 949	4, 219	637, 273	332, 115	7, 553, 263	12, 585, 705
Bonner Boundary Butte	113	11 2 2	47, 072 39, 673 1, 551	1, 600 16, 000	713, 712 2, 088, 000 70, 400	27, 700
Camas Custer Elmore	$\begin{array}{c} -2\\ 3,619\\ 1,559 \end{array}$	481 10, 452	101 153, 600 88, 224	24, 544	2, 979, 012	300 1,095,000
Gem Idaho Lemhi Owyhee	2, 122 141 1, 065	2, 906 1, 813 2, 050	21, 421 5, 367 33, 113	10, 868 2, 500 68, 200	89, 700 2, 000 89, 400	5, 000
OwyheeShoshoneValley	3, 709 354, 290 9, 210	3, 414 2, 579 2, 700	327, 857 12, 819, 649 144, 059	193, 200 5, 961, 767 26, 000	124, 700 207, 611, 671 244, 000	2, 970, 000 156, 515, 672 611, 000
Total, 1941	406, 954 353, 372	30, 649 51, 396	14, 319, 082 16, 091, 846	6, 636, 794 6, 627, 749	221, 566, 560 201, 796, 985	173, 810, 377 158, 030, 826
	BY CLA	sses of C	CONCENTE	RATES		
Dry gold	5, 018 7, 876	18, 341 5, 092	121, 707 314, 016 332	13, 745	98, 801	
Dry silver Copper Lead Lead-copper	8, 091 184, 158 2, 686	1 164 2,597 323	6, 374, 672 5, 554, 027 960, 127	4, 307, 400 996, 769 438, 782	173, 250 206, 832, 549 614, 092	
ZincZinc-lead	145, 601 38, 009 15, 514	1, 284 331 2, 516	501, 547 191, 310 301, 344	553, 034 113, 853 213, 211	7, 327, 017 6, 208, 738 312, 113	139, 524, 410 34, 285, 967
	406, 954	30, 649	14, 319, 082	6, 636, 794	221, 566, 560	173, 810, 377

#### Gross metal content of Idaho crude ore shipped to smelters in 1942, by classes of ore

		Gross metal content									
Class of ore	Ore	Gold	Silver	Copper	Lead	Zinc					
Dry and siliceous gold	Short tons 2, 266 11, 252 11, 403 1, 650 7, 234 83 2, 655 66	Fine ounces 1, 541 1, 001 36 151 85	Fine ounces 3, 193 37, 848 64, 453 27, 310 156, 453 12, 354 987 904	Pounds 6, 303 4, 593 11, 757 167, 221 39, 819 8, 333 11, 604 400	Pounds 1, 352 85, 083 867, 357 12, 128 5, 512, 430 38, 434 37, 515 13, 930	Pounds					
Total, 1941	26, 609 32, 533	2, 820 4, 492	303, 502 548, 787	250, 030 655, 222	6, 568, 229 8, 466, 662	975, 618 168, 08					

# Mine production of metals from Idaho crude ore shipped to smelters in 1942, in terms of recovered metals

#### BY COUNTIES

	Ore	Gold	Silver	Copper	Lead	Zinc
	Short	Fine	Fine			
	tons	ounces	ounces	Pounds	Pounds	Pounds
dams	89	16	547	35, 900	100000	1 United
Blaine	3, 827	840	15, 317	7, 885	93, 137	7, 29
Boise	334	924	33, 535	2, 100	25,000	1, 20
Bonner	72	î	7, 627	600	66, 888	
amas	399	263	8, 726	700	14, 598	
lark	24		66		13, 300	
Juster	4, 093	327	55, 462	131, 456	337, 988	513, 000
Imore	1,000	38	28		55.,500	
lem	52	3	75	132	1,000	
daho	61	136	147	600	400	
Cootenai	2		14		900	
emhi	1,386	127	8, 714	4,800	354,600	72,00
)wyhee	35	79	1, 151			
hoshone	15, 886	47	157, 631	24, 233	5, 335, 329	109, 32
alley	34	17	7,681		3,600	l
Vashington	310	2	6, 781	14, 800	4,700	
	26, 609	2, 820	303, 502	223, 206	6, 251, 440	701, 62
otal, 1941	32, 533	4, 492	548, 787	614, 251	8, 031, 015	137, 174
	В	CLASSES	OF ORE			
	0.000	1 541	2 102	0.010	000	
ory and siliceous gold	2, 266	1, 541	3, 193	6,018	888	
ory and siliceous gold-silver	1, 252	1,001	37, 848	3, 291	60, 526	
Pry and siliceous silver	11, 403	36 151	64, 453	10, 554 162, 253	807, 519 8, 090	
Copper	1,650	85	27, 310		5, 292, 395	
ead	7, 234 83	80	156, 453 12, 354	32, 620 7, 262	36, 515	
ead-copper		5	987	7, 202 858	-32, 257	661, 28
inc_lead	2, 655 66	1	904	350	13, 250	40, 33
IIIC-ICAU	. 00	- 1	301	300	10, 200	=0,00

#### REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, lead, and zinc in Idaho in 1942, by counties and districts, in terms of recovered metals

County and district		produc- ng	Ore sold		Gold			Silver		Copper	Lead	Zine	Total value
	Lode	Placer	or treated	Lode	Placer	Total	Lode	Placer	Total				
Ada County: Black Hornet			Short tons	Fine ounces 20	Fine ounces	Fine ounces 20	Fine ounces	Fine ounces	Fine ounces	Pounds	Pounds	Pounds	\$786
Boise Snake River Adams County: Seven Devils Benewah County:		3	89	16	492	492 16	547	31	31 547	35, 900			140 17, 242 5, 293
Tyson Creek (Camas Cove)	16			546 25	14	14 546 25	11, 302 1, 672		11, 302 1, 672	7, 000	79, 700 1, 400	72, 400	490 40, 067 2, 158
Sawtooth (Vienna) Warm Springs Boise County; Banner Boise Basin		1	112, 018	1, 300	13, 112	4, 488 1 14, 412	639, 616	3, 250	639, 616	333, 000 2, 100	7, 565, 300	12, 520, 600	2, 323, 502 35 532, 596
Boise Basin Payette River Rabbit Creek South Fork of Payette River Summit Flat		1 1 2	411	297	1 12 1 1	1 12 1 304	135	7	7				35 425 35 10, 736
Bonner County: Pend d'Oreille Bonneville County: Mount Pisgah Boundary County: Port Hill Butte County:	4	2	12, 092 41, 353	3 11	33	3 33 11	54, 699 39, 673		54, 699 39, 673	2, 200 16, 000			91, 568 1, 155 170, 429
Dome	3		1, 500 259	2		2	1, 011 540		1, 011 540		57, 000 13, 400	27, 700	4, 538 3, 928
Little Smoky and Carrietown Skeleton Creek Clark County: Birch Creek Clearwater County;	1	2	381 23 24	19 <b>244</b>		21 244	8, 713 114 66		8, 713 114 66	700	15, 300	300	8, 069 8, 621 938
Burnt Creek Moose Creek and Independence Creek Pierce	i	i			1 3 18	1 3 18		7	7				35 105 635
Custer County: Alder Creek Bayhorse Stanley and Stanley Basin	2 8 1	1 1	3, 429 39, 266 2, 000	143 61 306	10 1 2	143 62 308	2, 551 193, 379 3, 046		2, 551 193, 379 3, 046	104, 000 51, 800	27, 600 3, 288, 700 700	513, 000 1, 095, 000	68, 961 468, 130 12, 993
Yankee Fork	8	3	3, 266	887	4, 790	5, 677	13, 611	2, 416	16, 027	200			210, 116

Elmore County:						187							
Bear Creek	١.	1 -			1	1	1	1	1 2 1 2 2		1	1 22 2 2 1	ı i y
	4	3	116	53	2	55	45		45				1, 957
Boise River (Twin Springs)		. 4			2	2							70
Middle Boise	4	6	87, 872	23, 106	6, 385	29, 491	94, 666	2, 160	96, 826				1, 101, 039
Pine Grove	1		1	7		7	7		7				250
Snake River Gem County: West View		2			21	21							735
Gem County: West View	3	2	6, 843	2,909	8	2, 917	21, 496		21, 496	11, 000	90, 700	5, 000	125, 254
Idaho County:		1				1				,000	00,100	0,000	120, 201
Burgdorf-Marshall Lake	4	2	3, 144	1,600	15	1,615	4, 552	7	4, 559	200	400		59, 818
Camp Howard (Salmon River)		. 7			32	32		7	7	-00	100		1, 125
Dewey-Harpster	1		43	3		3	24	1	24	600			195
Dixie	3	7	155	73	221	294	45	38	83		3		10, 349
Elk City	4	13	232	56	5, 845	5, 901	263	1.087	1, 350				207, 495
Florence and French Creek		. 10			26	26		7,007	2,000				915
Lolo Creek		. 4	l		11	11							385
Lower Salmon River		. 3			68	68		14	14				2, 390
Newsome		2			512	512		111	111				17, 999
Orogrande	5	1	115	130	955	1. 085	111	204	315		400		38, 226
Ramey Ridge	1		3,000	825		825	218	201	218	1, 100			
Salmon River (Shoup) Simpson (Salmon River)		2	5,000	0.00	11	11	210		210	1, 100			29, 163
Simpson (Salmon River)		7			20	20							385
Suake River		l i			15	15							700
Ten Mile	6	l	5, 218	1, 089	1	1.089	1, 170		1, 170	1, 200			525
Warren	Ā	10	146	91	1. 176	1, 267	1, 170	384	1, 170 422	1, 200	1, 600		39, 199
Jerome County: Snake River		īž	110		38	38	00	904	422				44, 645
Kootenai County: Wolf Lodge	1		2		•		14		14				1, 330
Latah County:			~ "				14		14		900		70
Hoodoo		3		1.0	6, 012	6,012		329	, ,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,				
_ Moscow Mountain		ĭ			9,012	9,012	7-7	329	329				210, 654
Lemhi County:					9	9							315
Blue Wing	1		25, 340	9		9	31, 566		01 700				
Euraka	· 2	2	1, 040	82	17	99	31, 500		31, 566	39, 600	76, 000		32, 646
Gibbonsville (Dahlonega)	2	โ	74	25	4. 415	4, 440	90		90	28, 400			6, 965
Indian Creek	ĩ		15	6	4, 410	4,440	14	329	343				155, 644
Junction	î		26	١٠		0.							210
Kirtley Creek	-	7	20.		21	21	142		142	200	7, 300		614
Mackinaw	1	ģ	2	i	72								735
Mineral Hill	2		20, 015	2, 074	12	73		7	14		200		2, 578
Nicholia	1		434	2,074		2,074	1, 485		1, 485	200	13, 400		74, 568
Parker Mountain	1		404	3		2	526		526	600	13, 700	72,000	8, 131
Salmon River	-		1	. 0		3	14		14				115
Texas	2		1. 300	75	6	_6							210
Unorganized (Reno)	1		1, 300	75		75			7, 920	3, 800	325, 700		30, 539
Yellow Jacket	2		41	35					31		7,700		538
Lewis County:	4		41	30		35	69		69	200			1, 298
Clearwater River (Kamiah)	- N						11.4						-, -, -, -, -,
		2			2	2 3							70
Owyhee County:	· <b></b>	1			3	3							105
Carson or French	7		<b>70</b> 000	0 000									
Castle Creek	1		72, 096	3, 266	14	3, 280	206, 294	31	206, 325 .				261, 520
			225	51		51	59		59 .				1, 827
Flint Snake River	1		13	1		1 4	332		332				271
Couth Mountain		3			4								140
South Mountain	1		11, 188	212		212	122, 355		122, 355	193, 200	124, 700	2, 970, 000	402, 370
											,	_, 0.0, 000	202,010

Mine production of gold, silver, copper, lead, and zinc in Idaho in 1942, by counties and districts, in terms of recovered metals—Continued

County and district	Mines j		Ore sold					Silver		Copper	Lead	Lead Zinc	
	Lode	Placer	or treated	Lode	Placer	Total	Lode	Placer	Total				
			Short tons	Fine ounces	Fine ounces	Fine ounces	Fine ounces	Fine ounces	Fine ounces	Pounds	Pounds	Pounds	
Shoshone County: Beaver	8	3	83, 513	119 3	7 12	126 15	141, 923		141, 923	73, 700	5, 747, 600	8, 883, 300	\$1, 325, 487 530
Coeur d'Alone Evolution Hunter Lelande Plaçer Center	6 5 7 6		417, 898 557, 225 412, 686 141, 746	278 404 540 247		278 404 540 247	7, 341, 871 1, 085, 833 1, 580, 026 368, 730		7, 341, 871 1, 085, 833 1, 580, 026 368, 730	4, 626, 100 319, 300 414, 200 108, 600	413, 700 50, 372, 700 56, 506, 000 15, 213, 700	185, 600 68, 124, 300 26, 458, 700 14, 930, 100	5, 835, 353 10, 535, 454 7, 439, 153 2, 691, 811
St. JoeSummitYrekaTwin Falls County; Snake RiverValley County:	16	1 13	714, 348	1, 035	10 33 37	10 33 1,035 37	2, 458, 890	7	2, 458, 890 7	444, 100	84, 693, 300	38, 043, 000	350 1, 160 11, 050, 955 1, 300
Big Creek	1	1	7, 733	12 80	2	12 80 2	14 41, 549		14 41, 549	26, 000	244, 000		108, 663 70 70
South Fork of Salmon River————————————————————————————————————	1 1 1	2 2	9, 500 32 96, 861	943 5 2, 620	44	987 5 2, 620	609 7, 667 102, 510	31	640 7, 667 102, 510		3, 600		35, 000
Washington County: Snake River Washington (Mineral Creek)		1	310	2	1	1 2	6, 781		6, 781	14, 800	4, 700		35 6, 998
Total Idaho	203	236	2, 900, 704	50, 440	44, 580	95, 020	14, 634, 419	10, 471	14, 644, 890	6, 860, 000	227, 818, 000	174, 512, 000	46, 063, 326

Comment on districts with small production has been omitted owing to lack of space.

#### ADA COUNTY

Snake River district.—Dry-land dredging at three properties in Ada County near Grand View in 1942 recovered 492 fine ounces of gold and 31 fine ounces of silver. Cecil Rhodes operated the Eldridge and Hot Shot groups and John R. Rhodes the Dixie property.

#### ADAMS COUNTY

Nearly all the output in Adams County in 1942 was copper ore (80 tons) containing gold and silver from the Helena, Lucky Strike, and South Peacock properties near Cuprum in the Seven Devils district.

#### BLAINE COUNTY

Mineral Hill and Camas district.—The most important mining operation in the Mineral Hill and Camas district in 1942 was by the Lurline Mining Co. at the Camas property, 10 miles west of Hailey; shipments of gold ore during the last 4 months of 1942 totaled 1,460 tons. The remainder of the district output was principally old tailings from the Minnie Moore and Triumph properties and gold ore from the Treasure Vault mine.

Warm Springs district.—Mining of zinc-lead-silver ore from the Triumph-North Star-Independence groups near Ketchum by the Triumph Mining Co. continued to be the most important mining operation in southern Idaho; however, the grade of the ore in 1942 was lower than in 1941. The old 300-ton concentration mill at the North Star mine, which was remodeled in 1941, treated 32,512 tons of low-grade marginal zinc-lead-silver ore in 1942 that could not be mined at a profit in 1941. In addition, 78,148 tons of zinc-lead-silver ore were shipped to custom mills at Bauer and Tooele, Utah. The company was granted a basic quota of about 550 tons of lead and 900 tons of zinc a month. The quota has been revised several times, and as of May 1943 the company was still seeking further revisions. The rest of the district output was mainly gold-silver ore (771 tons) from the Red Cloud mine and gold ore (438 tons) from the June Day mine.

#### BOISE COUNTY

Boise Basin district (Centerville, Placerville, Idaho City, Pioneerville, Quartzburg).—When the price of gold rose to \$35 an ounce in 1935, placer mining, especially bucket dredging, became the most important type of mining in the Boise Basin district; it attained a record output of 22,990 ounces of gold in 1940 but declined to 13,112 ounces in 1942. All bucket dredging ceased in October 1942 owing to the gold-mine closing order of the War Production Board. The Fisher-Baumhoff Co., operating two bucket dredges at Centerville, remained the largest producer of placer gold in the State; the two dredges washed about 1,500,000 cubic yards of gravel and recovered 7,087 fine ounces of gold and 1,788 fine ounces of silver. The Idaho-Canadian Dredging Co. operated its 7½-cubic foot bucket dredge at Idaho City until October 15 and recovered 5,579 fine ounces of gold and 1,368 fine

ounces of silver from 1,394,695 cubic yards of gravel. The rest of the district placer gold was recovered largely by hydraulicking and sluicing at the White Rose, Moe, Fairchild, and Bell Flower properties. The output of lode mines in the district was chiefly high-grade gold-silver ore (269 tons) from the Come-Back mine at Pioneerville. Producers of gold ore included the Coin Bond, Hay Fork, Julian, Mineral Hill, Summit, and Texida properties.

Summit Flat district.—The output of 304 ounces of gold and 135 ounces of silver in the Summit Flat district in 1942 was chiefly lode gold recovered by amalgamation from ore mined at the King, Golden

Chariot, San Cristobal, and Viking properties.

#### BONNER COUNTY

Pend d'Oreille district.—The Whitedelf mine near Clark Fork, the largest producer of silver and lead in the Pend d'Oreille district in 1941, was closed in May 1942 owing to difficulty in obtaining adequate labor and supplies. During the first 4½ months of 1942 about 1,700 tons of silver-lead ore were treated in the company 50-ton flotation plant. The Hope (Elsie K.) mine, also near Clark Fork, was operated throughout 1942 by Hope Silver-Lead Mines, Inc.; 10,320 tons of ore containing 18,500 ounces of silver, 709,350 pounds of lead, and 326,800 pounds of zinc were treated in the company 150-ton flotation plant. In 1942 the company added more flotation equipment to the mill and did considerable metallurgical work in endeavoring to recover the zinc; however, no zinc concentrates were marketed in 1942. Small lots of high-grade silver ore were produced from the Brown Bear mine and lead ore from the Lawrence mine.

#### BOUNDARY COUNTY

The Idaho-Continental mine in the Port Hill district was operated continuously in 1942 by Trueman Higginbotham; 41,353 tons of ore containing about 45,000 ounces of silver, 2,450,000 pounds of lead, and a little gold and copper were treated in a 90-ton flotation mill.

#### BUTTE COUNTY

Lava Creek district.—The output of the Lava Creek district in 1942 was 153 tons of zinc ore from the Multa Metals group near Arco and 106 tons of zinc-lead ore from the Hornsilver and Moran mines. All the ore was shipped to a custom milling plant in Utah.

#### CLEARWATER COUNTY

Virtually all the output in Clearwater County in 1942 was placer gold recovered from stream gravel at various claims in the Burnt Creek, Independence Creek, and Pierce districts. The chief operation consisted of dredging gravel at the Meadow claim on French Creek in the Pierce district.

#### CUSTER COUNTY

Alder Creek district.—Lessees operated the White Knob property, 4 miles south of Mackay, in 1942 and shipped 2,109 tons of crude zinc ore to the International slag-fuming plant at Tooele, Utah, and 46 tons of silver-lead ore to a smelter; shipments of zinc ore to the slag-fuming plant ceased in July. The rest of the district output was crude

copper ore (1,274 tons) shipped from the Empire mine at Mackay. This mine was closed in August, but in December the Federal Bureau

of Mines started a drilling project.

Bayhorse district.—The mining of zinc-lead ore at the Clayton mine by Clayton Silver Mines in 1942 was the most important operation in the Bayhorse district. In May the company completed installation of additional milling equipment for recovering zinc, and during the last 7 months of the year lead concentrates and zinc concentrates were shipped to smelters; only lead concentrates were produced during the first 5 months. The mill treated 38,014 tons of ore containing 146,443 ounces of silver, 3,120,000 pounds of lead, 3,193,000 pounds of zinc, and a little gold and copper. The remainder of the district output was largely lead-silver ore (225 tons) and copper-silver ore (208 tons) from the Ramshorn mine and lead ore (624 tons) from the South Butte mine.

Stanley and Stanley Basin district.—The Valley Creek property near Stanley was operated a few months in 1942 by the Western Gold Exploration Co.; about 2,000 tons of gold ore were concentrated, and

nearly all the concentrates were cyanided.

Yankee Fork district.—Placer gold recovered by bucket dredging was the principal output of the Yankee Fork district in 1942. The 8-cubic foot bucket dredge of the Snake River Mining Co. at Sunbeam washed 1,428,326 cubic yards of gravel, which yielded 4,787 fine ounces of gold and 2,412 fine ounces of silver; operations ceased in October owing to Government regulations. The lode output of the district was chiefly gold-silver ore (3,224 tons), treated by amalgamation and concentration, from the General Custer-Lucky Boy group; this property was shut down May 1. About 20 tons of high-grade gold ore (some lots averaging 9 ounces of gold to the ton) were produced from the Fourth of July claim. Other gold producers included the Bachelor Mountain, Last Chance, and Yankee Fork properties.

#### ELMORE COUNTY

Middle Boise (Atlanta) district.—In 1942, as in 1941, the Middle Boise district was the largest gold-producing area in the State, resulting chiefly from operation of lode property (Boise-Rochester-Monarch groups) by Talache Mines, Inc. The company treated 87,747 tons of gold ore in its 400-ton amalgamation and concentration mill compared with 121,355 tons in 1941. In addition to gold and silver, the ore contains arsenic and tungsten; in 1942 some tungsten concentrates were produced and marketed. The rest of the district output was principally placer gold, recovered chiefly by the 7½-cubic foot bucket dredge of Boise King Placers. The dredge treated 1,310,879 cubic yards of stream gravel in 1942 and recovered 6,346 fine ounces of gold and 2,149 fine ounces of silver; operations ceased October 30.

#### GEM COUNTY

West View district.—In 1942 gold ore (6,650 tons) from the Lincoln group at Pearl was the most important output in the West View district. The mine and 75-ton flotation mill were operated until December 15, when operations ceased, probably for the duration of the war. The remainder of the district output was largely zinc-lead ore (141 tons) from the Friday mine.

#### IDAHO COUNTY

Burgdorf-Marshall Lake district.—The Golden Anchor Mining Co. operated its mine and 50-ton amalgamation-concentration plant at Czizek until April 30, 1942, when operations were closed permanently; 2,827 tons of gold ore were treated in 1942 and yielded 1,498 ounces of gold and 4,482 ounces of silver. The mine had been a large producer of gold since 1935. Gold ore was produced also from the Gold Crest, Jewell, and Leadville properties. The district output of placer gold and silver was recovered by hydraulicking and sluicing at the Ruby and Black Creek claims.

Dixie district.—A dragline floating dredge operated a few months in 1942 at the Dixie Placers and recovered 196 fine ounces of gold and 36 fine ounces of silver. The rest of the district output was principally

lode gold from the Slip Easy and Ontario properties.

Elk City district.—Four dredges (three dragline and one bucket-line) in the Elk City district treated 919,880 cubic yards of gravel in 1942 and recovered 5,805 fine ounces of gold and 1,083 fine ounces of silver. The bucket-line dredge (on Crooked River), operated by H. & H. Mines, was again the largest producer; it operated from January 1 to June 20 and recovered 2,859 fine ounces of gold and 560 fine ounces of silver. The dragline dredges, operated by the American River Mining Co. and the Tyee Mining Co., were also large producers of gold. Nearly all the lode output of the district was gold ore cyanided (220 tons) from the Blue Ribbon mine.

Newsome district.—Gold Hill Placers operated its dragline floating dredge on Newsome Creek 3 months in 1942 and recovered 500 fine ounces of gold and 105 fine ounces of silver from 82,000 cubic yards of gravel. A little placer gold and silver was produced from the Hay

Fork claim.

Orogrande district.—The principal output in the Orogrande district in 1942 was placer gold recovered from a property on Crooked River by the 2-cubic foot bucket dredge of the Mt. Vernon Co.; the dredge treated 167,966 cubic yards of gravel from March 15 to August 8 and recovered 955 fine ounces of gold and 204 fine ounces of silver. The lode output of the district was largely old mill cleanings from the Penman and Orogrande-Frisco mills.

Ramey Ridge district.—The Snowshoe mine near Big Creek was the only producer in the Ramey Ridge district in 1942; about 3,000 tons of gold ore were treated in a 25-ton amalgamation and concentration

mill.

Ten Mile district (Golden).—All the output in the Ten Mile district in 1942 was gold ore, chiefly from the Center Star mine. Lessees operated the mine and treated about 4,900 tons of gold ore in a 50-ton gravity-flotation mill; the jig concentrates were treated by amalgamation, and the flotation concentrates were shipped to a smelter. Other producers of gold ore included the Blackbird, Bob, Lone Pine,

and Shamrock properties.

Warren district.—The principal output in the Warren district in 1942 was placer gold recovered by the 2½-cubic foot bucket-line dredge operated on Warren Meadows by W. W. Prather; the dredge treated about 215,000 cubic yards of gravel and recovered 1,090 fine ounces of gold and 358 fine ounces of silver. Other placer producers included the Cook, Smith Gulch, and Steamboat properties. Nearly all the output from lode mines in the district was gold ore (amalgamated) from the Rescue mine.

And the second s

#### LATAH COUNTY

Hoodoo district.—In 1942, as in 1941, the output of the Hoodoo district was placer gold and silver, virtually all recovered by the 4½-cubic foot bucket-line dredge of Northwest Goldfields. The dredge operated from January 1 to October 14 and treated 1,021,726 cubic yards of gravel.

LEMHI COUNTY

Blue Wing district.—The Ima mine at Patterson, only producer in the Blue Wing district, was operated continuously in 1942 by the Ima Mines Corporation; 25,340 tons of ore containing 45,612 ounces of silver, 75,000 pounds of copper, 126,000 pounds of lead, 506,000 pounds of iron, and 253,000 pounds of tungsten were treated in a 150-ton gravity and flotation mill equipped with a magnetic separator. Iron concentrates (640 tons) containing chiefly silver, copper, and lead were shipped to a smelter in Utah, and tungsten concentrates (113 tons) were shipped to an eastern market.

Eureka district.—Lessees operated the Pope-Shenon mine a few months in 1942 and treated 560 tons of copper ore in a concentration mill. Gold ore (480 tons) from the Queen of the Hills mine was amalgamated. The rest of the district output was placer gold re-

covered from the Best Bet and Queen Gulch properties.

Gibbonsville district.—The principal output in the Gibbonsville district in 1942 was placer gold recovered chiefly by two dredges. A dragline floating dredge (Smith Bros.) at the Hagel property recovered 2,466 fine ounces of gold and 203 fine ounces of silver from 415,000 cubic yards of gravel, and a 4-cubic foot bucket-line dredge (Idaho-Warren Dredging Co.) at the Hughes Creek Placer recovered 1,900 fine ounces of gold and 123 fine ounces of silver from 380,000 cubic yards of gravel. The lode output of the district was gold ore from the Nevada and Red Star mines.

Mineral Hill district.—Gold Producers, Inc., continued in 1942 to operate the Grunter open-pit mine at Shoup and treated about 20,000 tons of gold ore by flotation. A little high-grade gold ore (15 tons)

from the Rico claim was shipped direct to a smelter.

Nicholia district.—Lessees operated the Viola mine near Reno and shipped 434 tons of carbonate zinc ore to the International slag-

fuming plant at Tooele, Utah.

Texas district.—The principal output in the Texas district in 1942 was 820 tons of crude silver-lead ore from the Latest Out mine near Gilmore.

#### OWYHEE COUNTY

Carson district (Silver City, De Lamar).—The De Lamar Milling Corporation operated its 250-ton flotation mill continuously in 1942 until December 22, when the plant was closed permanently; 72,052 tons from De Lamar waste dumps were treated, and the resulting high-grade gold-silver concentrates (274 tons) were shipped to a smelter in Utah. The rest of the district output was largely gold ore from the Pauper and South Central properties.

South Mountain district.—Mining operations by the South Mountain Mining Co. at the Golconda mine were continuous throughout 1942. The company shipped 11,188 tons of ore containing 260 ounces of gold, 132,243 ounces of silver, 225,718 pounds of copper, 139,610 pounds of lead, and 3,870,161 pounds of zinc to the International

flotation mill at Tooele, Utah.

#### SHOSHONE COUNTY

#### COEUR D'ALENE REGION

The value of the metal output of the Coeur d'Alene region was \$38,880,253 in 1942, a 20-percent gain over 1941. The output of lead increased 11 percent, zinc 15 percent, and copper less than 1 percent; gold decreased 21 percent and silver nearly 12 percent. The output of zinc in 1942 exceeded the former record of 1941, and the output of lead was the largest since 1930.

Calculated from reports of production for the first quarter of 1943 and of new producers of zinc, the output of zinc in 1943 should be about 4 percent greater than in 1942; however, the output of lead will be less.

The chief producers of zinc in the region in 1942, according to rank (each producing more than 11,000,000 pounds), were the Star, Morning, Hecla, Bunker Hill & Sullivan, Tamarack, and Page properties; the chief producers of lead, according to rank (each producing more than 10,000,000 pounds), were the Bunker Hill & Sullivan, Hecla, Morning, Page, Star, Sherman, and Tamarack properties. Nearly 71 percent of the material produced in the Coeur d'Alene region in 1942 was zinc-lead ore and old tailings, more than 18 percent silver ore, and 10 percent lead ore. Nearly all mines worked 6 days a week and milling plants 7 days a week. Miners' wages increased from \$6.25 a shift in March 1941 to \$8.25 a shift in May 1942, the highest ever paid in the district. In 1942 the region was the largest silverproducing area in the United States; it ranked second in lead and third in zinc.

Mine production of gold, silver, copper, lead, and zinc in the Coeur d'Alene region, Shoshone County, 1941-42, and total, 1884-1942, in terms of recovered metals

Year	Mines producing		Ore	Gold (lode	Silver (lode and	Copper	Lead	Zinc	Total
	Lode	Placer		and placer)	placer)				value
1941 1942	58 49		Short tons 2, 051, 390 2, 327, 417				Pounds 191, 057, 000 212, 947, 000		
Total, 1884–1942			(1)		400, 543, 895				978, 091, 576

Figures not available.Short tons.

Beaver district.—All the lode output (83,513 tons of ore) in the Beaver district in 1942 was zinc-lead ore; the chief producers were the Interstate-Callahan mine and waste dump, the Sunset mine, and the Amazon-Manhattan group. The Daylight Lease operated the Interstate-Callahan mine throughout the year and hauled 26,029 tons of ore containing principally silver, lead, and zinc to Zanetti Bros. flotation mill near Wallace; 17,453 tons of similar ore from the mine waste dump, operated by Zanetti Bros., were treated in the same mill. About 20,200 tons of zinc-lead ore from the Sunset mine were treated in the Golconda 250-ton custom flotation mill near Wallace. lead ore (11,115 tons) from the Amazon-Manhattan group was treated in the Dayrock and Hercules custom mills, also near Wallace. producers of zinc-lead ore were the Silver Tip (Portland), Port Arthur, Monarch, and Sitting Bull properties.

Evolution district.—The principal output in the Evolution district in 1942 was silver ore (414,019 tons) from the Sunshine. Mineral Point, and Polaris properties near Osburn. The chief producer was the Sunshine mine, although its output of silver ore decreased from 305,180 tons in 1941 to 251,700 tons in 1942 and the production of silver from 7,138,426 to 4,976,859 ounces. According to the printed annual report of the Sunshine Mining Co., the decrease in tonnage of ore mined was due to a labor shortage. A constructive step was taken by the Army to relieve the shortage by releasing soldiers with previous coal- and metal-mine experience for employment in nonferrous metal mines. Late in the fall 109 furloughed soldiers were employed at the Sunshine mine, and more could be used. tions point to a further shortage of labor during the spring of 1943, and production depends more on manpower than any other factor. In March 1942 the company started to construct a plant to recover, by leaching and electrolytic deposition, the antimony contained in the high-grade silver-copper-antimony concentrate. A pilot antimony plant operated through May, when it was shut down for the transfer and installation of its equipment at the new full-sized plant. During the 5 months operated, the pilot plant produced 142,400 pounds of antimony metal. The new plant began operating the middle of September and has processed the total tonnage of silvercopper-antimony concentrate produced since September 1; to the end of the year it had produced 250,000 pounds of antimony metal. The residue remaining after the antimony had been leached was shipped to a copper smelter for the recovery of the silver and copper content. In 1942 the 1,200-ton differential flotation plant produced 3,121 tons of high-grade silver-copper-antimony concentrates and 4,329 tons of low-grade silver-iron concentrates. The ore reserves are estimated at 583,000 tons—a decrease of 167,000 tons from the estimate of 1941. The 600-ton flotation mill at the Mineral Point mine of the Coeur d'Alene Mines Corporation treated 122,301 tons of silver-copper-antimony ore in 1942. The company reported that ore was mined on all levels from the 600- to the 1,800-foot, inclusive. A raise driven from the 600-foot level shows a good grade of ore for 300 feet above the level. Drifting west on the 1,600- and 1,800-foot levels shows a lengthening ore shoot to the west, and a major portion of ore output is now coming from the two levels. The concentrates (4,914 tons) contained 1,586,460 ounces of silver, 3,132,398 pounds of copper, and 1,839,936 pounds of antimony. The property was the largest producer of copper in Idaho and ranked second in antimony and third in silver. About 40,000 tons of silver ore from the Polaris mine were treated in the company 200-ton flotation mill; the contentrates contained 63 ounces of gold, 773,074 ounces of silver, 238,450 pounds of copper, 135,800 pounds of lead, 194,524 pounds of antimony, and some iron. The company reported that development in 1942 aggregated 1,977 feet, of which 879 feet were in ore and 1,098 feet in waste; ore reserves are estimated at 29,150 tons. The rest of the district output was virtually all old zinc-lead tailings (3,789 tons) from two dumps at Osburn.

Hunter district (Mullan).—In 1942, as in 1941, the output of recoverable zinc (68,124,300 pounds) in the Hunter district was larger than in any other district in Idaho; the chief producer was the Star mine of the Sullivan Mining Co. at Burke. The 1,000-ton flotation

mill at the mine treated 242,900 tons of ore yielding lead concentrates and zinc concentrates, which contained 240,069 ounces of silver, 16,678,000 pounds of lead, and 42,269,434 pounds of zinc; the mine was again the largest producer of zinc in Idaho. The company reported that the mine operated at capacity to June 1, when a shortage of labor began in the district; by September operations dropped to 50 percent of capacity. The output of zinc-lead-silver ore from the Morning mine of the Federal Mining & Smelting Co. at Mullan decreased to 236,902 tons in 1942 from 270,787 tons in 1941. The 1,250-ton flotation mill at the mine operated continuously in 1942 and yielded lead concentrates and zinc concentrates containing 200 ounces of gold, 622,530 ounces of silver, 32,405,528 pounds of lead, and 36,156,146 pounds of zinc. The mine ranked second in the State in zinc output and third in lead. According to the printed annual report of the company, the labor shortage became so acute during the summer that underground work at the mine was placed on a one-shift-a-day basis August 17. This continued until November 9, when some improvement in the labor supply permitted resumption on a two-shift-a-day basis; ore production during the summer was only about 50 percent of normal. In the last 6 months of 1942 operations at the mine resulted in earnings of only \$54,911 owing to increased operating expense and shortage of labor. In 3 of these months there was an actual operating loss. Were it not for the fact that the quota was reduced, it is doubtful if the Morning operations could be conducted at much profit and might result in an actual loss. Leasing operations at the Gold Hunter mine produced 65.417 tons of silver-lead ore in 1942, which was treated in the 500-ton Gold Hunter flotation plant. The rest of the district output comprised 6,756 tons of zinc-lead ore from the Golconda mine and 5,250 tons of similar ore from the Lucky Friday mine, all treated in the 250-ton custom flotation mill of Golconda Lead Mines near Wallace.

Lelande district (Burke, Mace, Frisco).—Zinc-lead-silver ore from the Hecla mine at Burke was, as usual, the most important output in the Lelande district in 1942. The company reported that 274,938 tons of zinc-lead-silver ore were treated in the 900-ton flotation plant at the mine, and 5,474 tons of crude silver-lead ore were smelted. The concentrates and crude ore contained 340 ounces of gold, 1,106,460 ounces of silver, 378,764 pounds of copper, 43,190,323 pounds of lead, and 25,570,047 pounds of zinc; the mine ranked second in the State in lead output, third in zinc, and fourth in silver. According to the printed annual report of the company, capacity operations at the Hecla mine were maintained for the first 8 months of the year, after which production was cut 15 percent. Development in 1942 totaled 3.576 feet, of which 2,316 feet were in ore and 1,260 feet in waste; no additional ore of importance was discovered. Ore reserves at the end of 1942 are estimated at 145,522 tons. Development and an increase in width in some stopes resulted in gaining some tonnage over the estimate for 1941. This, together with the decreased output per month, has extended the life of mine operations. Beginning about May 1, 1943, the declining tonnage from the mine will be supplemented in the mill with ore from the Silver Cable lease in Montana, and with old tailings deposited at Osburn, Idaho, estimated to contain 2,000,000 tons of material averaging about 34 pounds of lead and about 40 pounds of zinc to the ton. The company has touilt a sink-and-float plant on the property to handle 2,000 tons of material a day; this plant will reject approximately 40 percent as waste, and the remaining product will be treated at the Hecla and Polaris mills. It is expected that milling will begin about May 1, 1943.

The Sherman Lead Co. operated its mine and 300-ton flotation mill throughout the year. The company reported that 69,804 tons of ore were treated, containing 434,962 ounces of silver, 13,938,580 pounds of lead, and 3,000,000 pounds of zinc. Heretofore, no zinc has been recovered, but in November the mill started producing some zinc-lead concentrate in addition to lead concentrate. Leasing operations (Hull Lease) at the Frisco mine produced 27,067 tons of zinc-lead milling ore in 1942. In March 1942 the Federal Mining & Smelting Co., owners of the mine, began unwatering the lower levels, which have been flooded since 1916. Production by the company started November 1, and during the last 2 months of the year 2,770 tons of zinc-lead ore were treated in the Morning mill. The company reported that from the present outlook it is believed the mine will produce a substantial tonnage of zinc-lead ore in 1943. The remainder of the district output was largely old zinc-lead tailings (27,673 tons) deposited at various places along Canyon Creek above Wallace; 23,961 tons of tailings were hauled by the Small Leasing

Co. to the Golconda custom mill.

Placer Center district.—The chief output in the Placer Center district in 1942 was zinc-lead ore from the Tamarack mine, treated in the company 300-ton flotation mill. According to the printed annual report of the Tamarack & Custer Consolidated Mining Co., the mine produced 110,735 tons of ore in 1942 containing 203,522 ounces of silver, 11,897,235 pounds of lead, and 17,693,087 pounds of zinc. Despite the large production of ore in 1942 and the unfavorable results of development on the 2,000-foot level, the ore reserves were not seriously diminished at the end of the year. The average crew required at the Tamarack mine to maintain normal production and development is not less than 160 men. Only during the first 4 months and the last 2 months of 1942 was enough manpower available. Although production did not suffer greatly, development had to be decreased. The mine and mill are prepared for maximum production in 1943. The Dayrock Mining Co. operated its mine and 200-ton flotation mill continuously in 1942 and treated 26,278 tons of According to the printed annual report of the comsilver-lead ore. pany the ore contained 188,241 ounces of silver, 4,772,720 pounds of lead, and 750,000 pounds of zinc; however, no zinc was recovered. Ore reserves were substantially diminished in 1942, as new discoveries of ore were equivalent to only a fraction of the tonnage extracted during the year. The 500-foot level was extended westerly 578 feet but there is difficulty in tracing the Dayrock vein downward. remainder of the district output was mainly old zinc-lead tailings (2,823 tons) from a property near Wallace and zinc ore (2,200 tons) from the Success mine operated by lessees.

Yreka district (Kellogg).—The value (\$11,050,955) of the metal output of the Yreka district and the output of recoverable lead (84,693,300 pounds) in 1942 were larger than in any district of Idaho, and that of recoverable zinc and silver ranked second. Zinc-lead-silver ore from the Bunker Hill & Sullivan mine at Kellogg was, as usual, the principal output in the district; 408,549 tons of ore were

treated by gravity and flotation concentration and 68,833 tons of old tailings (silver-lead-iron) were treated by straight gravity con-The company reported that the lead concentrates and zinc concentrates produced from both ore and old tailings contained 1,657,425 ounces of silver, 60,087,300 pounds of lead, and 27,223,700 pounds of zinc. The property remained the largest producer of lead and second in output of silver in Idaho and was fourth in zinc. According to the printed annual report of the company, exploration in 1942 resulted in finding good ore in quantity at several points. The Emery vein, extensively mined on 21 level, has been cut 400 feet lower on the 23 (bottom) level of the mine and shows very well, both as to grade and quantity, with good promise for further deeper mine development. An important find of ore on 13 level was made in an area of the mine not heretofore prospected. Westward mining on 21 level continues to disclose ore of importance. Ore reserves on January 1, 1943, undercut and available for mining, totaled 2,839,620 tons of zinc-lead-silver ore—an increase of 109,222 tons over the ore reserves reported January 1, 1942.

The Blackhawk and Page mines and the Page 500-ton flotation mill were operated continuously in 1942 by the Federal Mining & Smelting Co. The company reported that 139,848 tons of zinc-lead ore from the Page mine and 14,992 tons of similar ore from the Blackhawk mine contained 602,319 ounces of silver, 24,526,600 pounds of lead, and 16,598,850 pounds of zinc. According to the printed annual report of the company "the labor shortage experienced by most of the companies in the Coeur d'Alene region did not affect seriously operations at these properties." Development on the 2,100 and 2,400 levels discovered ore shoots of excellent length and good average grade.


The 100-ton flotation mill at the Constitution mine (Spokane-Idaho Mining Co.) on Pine Creek operated throughout the year and treated 20,307 tons of zinc-lead ore. Milling of zinc-lead ore from the Highland-Surprise mine was begun in June and suspended in November; during the 5 months a total of 14,474 tons of zinc-lead ore was treated. The Little Pittsburg mine and its 100-ton flotation mill on Pine Creek were operated in 1942 by the Denver Development Co.; 11,656 tons of ore were treated, containing an average of 1.50 ounces of silver to the ton, 3.31 percent lead, and 8.32 percent zinc. The remainder of the district output was mainly 9,793 tons of old tailings (silver-lead) from the Sierra Nevada property, 7,983 tons of silver ore from the Crescent mine, 7,500 tons of zinc-lead ore from the Douglas mine dump, 3,700 tons of old zinc-lead tailings from various dumps, and zinc-lead ore from the Sidney and Liberal King mines.

#### VALLEY COUNTY

Deadwood Basin district.—The Hall-Interstate group, 54 miles east of Cascade, was operated in 1942 by the Callahan Zinc-Lead Co.; 7,733 tons of zinc-lead ore were treated by flotation, yielding 240 tons of silver-lead-copper concentrates and 590 tons of zinc concentrates.

Thunder Mountain district.—The output of the Thunder Mountain district in 1942 was 943 fine ounces of gold and 609 fine ounces of silver recovered from gold ore amalgamated from the Sunnyside-Dewey group and 44 fine ounces of gold and 31 fine ounces of silver recovered principally from the Bonanza placer on Mule Creek.

Yellow Pine district.—The practice of treating gold-silver-antimony-tungsten ore from the Yellow Pine mine was changed in 1942 from bulk sulfide flotation to selective flotation of antimony minerals from pyrite and arsenopyrite, and tabling of flotation-made tungsten concentrate was abandoned for improved flotation metallurgy. There were 96,861 tons of ore treated in 1942, containing an average of 0.039 ounce of gold and 1.41 ounces of silver to the ton, 4.79 percent antimony, and 2.59 percent tungsten. The 400-ton mill yielded 2,294 tons of high-grade tungsten concentrate, 6,887 tons of low-grade tungsten concentrate, 7,564 tons of gold-silver-antimony concentrate, and 816 tons of gold-antimony-iron concentrate. The capacity of the mill was increased to 800 tons of ore a day early in 1943.



# GOLD, SILVER, COPPER, LEAD, AND ZINC IN MONTANA

(MINE REPORT)

By G. E. WOODWARD AND PAUL LUFF

# SUMMARY OUTLINE

Page	Page
Summary 389	Metallurgic industry 396
Calculation of value of metal production 390	Review by counties and districts 400
Mine production by counties	
Mining industry 395	
Ore election 395	♣ Control of the

#### SUMMARY

Copper remained the chief source of metal value in Montana and was the only metal to show increased output in 1942. The aggregate value of the gold, silver, copper, lead, and zinc produced from Montana ores and gravels was, in terms of recoverable metal, \$60,129,853 This slight advance compared with \$59,181,627 in 1941 (see fig. 1). was due to a greater output of copper and a higher average price paid for copper, lead, and zinc in 1942. Gold and silver production-more particularly gold—was cut drastically by the widespread closing of gold mines in every section of Montana. The output of lead and zinc was affected seriously when all zinc-lead mines at Butte, operated by the Anaconda Copper Mining Co., closed in late May; however, this closing enabled the Anaconda Copper Mining Co. to maintain and even increase its output of copper. Silver Bow County, which includes the Butte area and yields nearly all the copper and most of the zinc and silver output of the State, produced gold, silver, copper, lead, and zinc valued at \$46,942,464 in 1942 compared with \$44,195,725 in This increase was due to the greater output of copper by the Anaconda Copper Mining Co.

Several factors influenced the production of metals in Montana dur-The great majority of the mining districts in Montana are ing 1942. primarily gold-producing; in consequence of, first, a serious labor shortage and, finally, the Government closing order issued in October, many of the large gold mines either shut down or greatly reduced their This labor shortage was first felt in several of the districts . in late 1941 or early in 1942 and prompted many gold producers, more particularly operators of lode mines, to make and carry out plans for suspending operations for the duration of the war even before the Government issued its closing order in October. Gold production from Beaverhead, Broadwater, Madison, Park, Lewis and Clark, Jefferson, Phillips, and Powell Counties was affected most.

A premium pay plan stimulated the production of copper, lead, and The plan, authorized by the Metals Reserve Company (a Government agency), effective February 1, 1942, granted producers of base metals a premium of 5 cents a pound for copper and 2% cents a pound for lead and zinc produced in excess of certain fixed basic quotas. plan was modified further to include one additional premium of 2% cents for lead and two additional premiums of 2% cents for zinc. The effective date of the modification was the opening of business Decem-Eligibility for these additional premiums was based upon ber 1, 1942. the producer's ability to maintain the present rate of production or to increase output, chiefly from marginal ore bodies. Each case was to be considered independently by the quota committee at Washington, D.C.

Although the Government stimulated the production of base metals by means of premium payments and successive reductions of quotas for various mining companies, the effect of the program was more than offset by the critical shortage of labor at mines, mills, and smelters. Several plans were tried to alleviate this shortage, including wage increases, taking miners from gold mines, stabilization of labor at mines, and the furloughing of soldier-miners to work in the The last plan was the most helpful action taken, although it, too, failed to satisfy the full need. During October and November over 4,000 soldiers were furloughed for service in western mines. Of this number, Montana received about 1,100 men, most of whom were employed at the copper mines at Butte. As these mines, operated by the Anaconda Copper Mining Co., had previously taken over miners from the closed zinc mines, the addition of the soldiers tended to raise the number employed at the copper mines to an operating minimum. The company still needed approximately 700 trained miners before the zinc mines could be reopened.

All tonnage figures are short tons and "dry weight"; that is,

they do not include moisture.

The value of metal production herein reported has been calculated at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zine 4
1938	Per fine ounce \$35.00 35.00 35.00 35.00 35.00	Per fine ounce  5 \$0.646+  6.678+  7.711+  7.711+  7.711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057 .067	Per pound \$0.048 .052 .063 .075

<sup>1</sup> Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.

\*Treasury buying price for newly mined silver.

\*1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Company for over-quota production but excludes value of foreign copper delivered to Metals Reserve Company for domestic consumption.

\*1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Company for over-quota production.

\*\$0.67878787.

\*\$0.67878787.

Mine production of gold, silver, copper, lead, and zinc in Montana, 1938-42, and total, 1862-1942, in terms of recovered metals

Year		Mine	s produc- ing	Ore (short tons)		Gold (lode a	nd placer)	Silver (lod	e and placer)
		Lode	Placer	МП		Fine ounces	Value	Fine ounce	s Value
1938		48 59 68 61 37	282 7 285 2 325	2, 724, 3, 792, 5, 099, 5, 642, 5, 678,	780 241 249	203, 313 264, 173 272, 602 246, 475 146, 892	\$7, 115, 955 9, 246, 055 9, 541, 070 8, 626, 625 5, 141, 220	6, 403, 96 9, 087, 57 12, 361, 05 12, 386, 92 11, 188, 11	1 6, 168, 533 0 8, 790, 080 5 8, 808, 480
1862-1942				(1)		16, 827, 410	373, 412, 562	724, 391, 02	8 529, 152, 667
		Co	pper		1	Lead	Z	ine	
Year	Pou	nds	Value	P	ounds	Value	Pounds	Value	Total value
1938 1939 1940 1941	154, 42 195, 65 252, 78 256, 07 282, 38	4,000 2,000 2,000	\$15, 133, 20, 348, 628, 564, 30, 216, 634, 168, 9	016   33, 366   46, 196   42,	654, 000 110, 000 072, 000 518, 000 100, 000	1,556,170 2,303,600 2,423,526	17, 688, 000 69, 598, 000 105, 174, 000 121, 420, 000 109, 430, 000	\$849, 024 3, 619, 096 6, 625, 962 9, 106, 500 10, 176, 990	\$28, 096, 746 40, 937, 870 55, 825, 078 59, 181, 627 60, 129, 853
1862-1942	<sup>2</sup> 6, 17	8, 651	1, 792, 068,	110 2	647, 292	69, 194, 368	2 1, 754, 382	264, 968, 420	3, 028, 796, 427

<sup>1</sup> Figures not available.

Gold and silver produced at placer mines in Montana, 1938-42, in fine ounces, in terms of recovered metals

	011-1			Dredges								
Year	Sluicing hydra	g and ulic	Drift n	ining	Dry-la	nd 1	Dragi floatii		Float buck		Tot	al
	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silve
1938 1939 1940 1941 1942	2 3, 896 2, 075 2, 163 2, 305 2, 732	232 272 353	281 139	(2) · 20 41 17	5, 721 9, 164 11, 252 14, 663 3, 674	2,722 2,640 2,408	9, 737 11, 439 10, 660	1,937 1,302 833	21, 356 33, 815 39, 012 33, 844 31, 283	6, 723 7, 400 6, 424	35, 348 54, 999 64, 147 61, 611 41, 242	11, 634 11, 655 10, 035

<sup>&</sup>lt;sup>1</sup> Floating washing plant supplied with gravel by a dragline excavator is called a "dragline dredge"; a stationary or movable washing plant supplied with gravel by any type of power excavator is called a "dry-land dredge."

<sup>2</sup> Figures for sluicing and hydraulic include those for drift mining.

Gold.—Montana ores and gravels yielded 146,892 fine ounces of gold in 1942 compared with 246,475 ounces in 1941—a 40-percent decrease; the output from lode mines decreased 79,214 ounces and from placer mines 20,369 ounces. Siliceous ores yielded 55 percent of the State total gold, and base-metal ores 17 percent; there was a decrease from all classes except copper ore. Losses in gold output were general throughout the State but were largest in Madison, Broadwater, Lewis and Clark, Silver Bow, Phillips, Park, and Beaverhead Counties; slight increases were noted in Flathead and Judith Basin Counties, but these counties have negligible importance as gold producers. Gold ore mined totaled 322,140 tons, compared with 695,481 tons in 1941, and included 251,939 tons treated in amalgamation and cyanidation mills, 30,873 tons in concentrating mills, and 39,328 tons shipped crude to smelters. Ore treated at amalgamation and cyanidation plants (with or without concentrating equipment)

<sup>2</sup> Short tons.

yielded 25 percent of the State total gold, that at concentrating mills 22 percent, ores of all classes shipped crude to smelters 25 percent,

and placers 28 percent.

The leading gold producers in Montana in 1942 (not representative of capacity to produce, but merely of good fortune in keeping adequate operating personnel) were the company-operated copper mines of the Anaconda Copper Mining Co. at Butte, the West Mayflower property in Madison County, the Winston dredge operating on Prickly Pear Creek near Clancey, the Ohio Keating mine in Broadwater County,




FIGURE 1.—Value of mine production of gold, silver, copper, lead, and zinc, and total value in Montana, 1870-1942.

Porter Bros. dredge near Helena, and the Perry Schroeder dredge on

Missouri River in Lewis and Clark County.

Silver.—The output of recoverable silver in Montana in 1942 was 11,188,118 fine ounces compared with 12,386,925 ounces in 1941—a 10-percent decrease. This loss in output can be attributed almost entirely to the closing of all zinc mines of the Anaconda Copper Mining Co. in late May 1942, as these mines produced over 1,000,000 ounces of recoverable silver during nearly 6 months of operation. Copper ore yielded 56 percent of the State total silver, zinc-lead ore 22 percent, siliceous ore 20 percent, and lead ore, zinc ore, and placers together 2 percent. Ore treated at concentration mills yielded 83 percent of the total silver, and crude smelting ore 16 percent. The output of silver ore was 134,153 tons and of gold-silver ore 77,231 tons.

Copper mines, dumps, tailings piles (at Anaconda), zinc mines at

Butte, and the Flathead mine in Flathead County, all operated by the Anaconda Copper Mining Co., produced 75 percent of the State total silver. Other large producers included the Granite-Bimetallic mine (tailings) in Granite County; the Lexington group in the Montana district, Cascade County; the Emma mine at Butte (including byproduct silver); and the St. Joseph Lead Co. property in Judith

Basin County.

Copper.—Copper produced in Montana in 1942, in terms of recoverable metal, was 282,388,000 pounds, compared with 256,072,000 in 1941—a 10-percent gain. This gain was due entirely to the greater output of the Anaconda Copper Mining Co., which again was the only important copper producer in Montana. All active copper mines at Butte are owned and operated by the Anaconda Copper Mining Co., except the property of the North Butte Mining Co. In 1942 this property was operated by the Anaconda Copper Mining Co. through contract agreement. Copper produced from all sources at Butte gained in 1942, except that derived from the treatment of mine dumps; the quantity from this source is comparatively small, and the loss was easily offset by gains elsewhere. Copper ore and precipitates yielded gold, silver, and copper valued at \$38,408,147, or 64 percent

of total State value. Lead and zinc.—The value of the production of lead and zinc in Montana, in terms of recoverable metals, increased in 1942 compared with 1941; however, the increases in total value were due to higher average price for the metals, as the quantities decreased. showed a 12-percent gain in value but a 10-percent decrease in quan-Lead showed an 11-percent gain in value but a 6-percent loss in The closing, on May 25, of all zinc mines at Butte operated quantity. by the Anaconda Copper Mining Co. was the chief cause of decreased output of both metals. This closing is calculated to have reduced the output of lead from Montana about 7,000,000 pounds and the output of zinc about 40,000,000 pounds. The output from the slag-fuming plant at East Helena operated by the Anaconda Copper Mining Co. increased in 1942 by 811,000 pounds in lead and 2,878,000 pounds in The Emma mine, operated by the Anaconda Copper Mining Co. under lease, reported a decrease of about 1,000,000 pounds in lead and 5,000,000 pounds in zinc from zinc-lead ore but a gain of about 3,600,000 pounds in lead and about 8,200,000 pounds in zinc as a byproduct.

In 1942 the leading sources of zinc, named in order of output, were the slag-fuming plant at East Helena, all zinc mines operated by the Anaconda Copper Mining Co. at Butte, the Emma byproduct zinc, the Poulin mine at Butte, the Mike Horse mine in Lewis and Clark County, the Emma mine at Butte, the St. Joseph Lead Co. property in Judith Basin County, and the Hecla slag dump in Beaverhead County; these sources supplied 96 percent of the State total. The leading lead producers in Montana in 1942 were all zinc mines at Butte, the Emma byproduct lead, the Mike Horse mine in Lewis and Clark County, the Jack Waite mine in Sanders County, the slag-fuming plant at East Helena, the St. Joseph Lead Co. property in Judith Basin County, the Flathead property in Flathead County, the Forest Rose properties in Granite County, and the Mount Washington mine in Jefferson County; these sources contributed 80 percent of the State total.

# MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in Montana in 1942, by counties, in terms of recovered metals

	Mines p	roducing	Gold (lode ar	nd placer)	Silver (lode and placer)		
County	Lode	Placer	Fine ounces	Value	Fine ounces	Value	
Beaverhead	27	10	4,808	\$168, 280	59, 736	\$42,479	
Broadwater		19	14, 853	519, 855	39, 652	28, 197	
Cascade		10	2, 765	96, 775	730, 620	519, 552	
Deer Lodge	- 5	1	2, 152	75, 320	5, 971	4, 246	
Fergus	5 2	2	1, 754	61, 390	744	529	
Flathead	. 3	-	370	12, 950	770, 206	547, 70	
Granite		10	11, 100	388, 500	584, 640	415, 74	
Jefferson		8	16, 048	561, 680	158, 535	112, 736	
Judith Basin	3		221	7, 735	216, 135	153, 696	
Lewis and Clark	51	25	22, 181	776, 335	298, 509	212, 27	
Lincoln		8	105	3, 675	2, 527	1, 79	
Madison		14	28, 324	991, 340	97, 283	69, 17	
Meagher		6	62	2, 170	7		
Mineral	1	19	76	2,660	270	19	
Missoula	ā	7	2,007	70, 245	391	278	
Park	3	ģ	9, 899	346, 465	34, 584	24, 59	
Phillips	4 3 2		5, 226	182, 910	38, 783	27, 579	
Powell	13	18	1, 465	51, 275	5, 452	3, 87	
Ravalli	1	ž	964	33, 740	66	. 4	
Sanders	4	1	131	4, 585	20, 219	14, 378	
Silver Bow	28	10	22, 381	783, 335	8, 123, 788	5, 776, 916	
	370	170	146, 892	5, 141, 220	11, 188, 118	7, 955, 998	
Total, 1941	612	325	246, 475	8, 626, 625	12, 386, 925	8, 808, 48	

County	Cor	per	Le	ad	Zi	ne	Total
	Pounds	Value	Pounds	Value	Pounds	Value	value
Beaverhead	106, 000 27, 000 32, 000 3, 000	\$12, 826 3, 267 3, 872 363	1, 578, 700 700, 700 2, 067, 000	\$105, 773 46, 947 138, 489	1, 500, 700 165, 600 1, 018, 700	\$139, 565 15, 401 94, 739	\$468, 923 613, 667 853, 427 79, 929
Fergus Flathead Granite Jefferson Judith Basin	101, 000 228, 000 89, 000 115, 000	12, 221 27, 588 10, 769 13, 915	1, 227, 700 1, 315, 600 1, 493, 300 3, 407, 000	82, 256 88, 145 100, 051 228, 269	1, 452, 000 1, 185, 000 1, 751, 000	135, 036 110, 205 162, 843	61, 919 655, 129 1, 055, 013 895, 441 566, 458
Lewis and Clark Lincoln	743, 000	89, 903 8, 833	8, 824, 000 114, 300 794, 300	591, 208 7, 658 53, 218	5, 300 18, 700	3, 991, 188 493 1, 739	5, 660, 907 13, 130 1, 123, 063 2, 175 5, 395
Missoula	700 148, 000	85 17, 908	126, 100	8, 449	95,000	8, 835	70, 608 406, 250 210, 489
RavalliSandersSilver Bow		2, 783 33, 964, 458	30, 700 3, 997, 600 14, 411, 000	2, 057 267, 839 965, 537	696, 000 58, 626, 000	64, 728 5, 452, 218	57, 366 33, 787 354, 313 46, 942, 464
Total, 1941	282, 388, 000 256, 072, 000		40, 100, 000 42, 518, 000	2, 686, 700 2, 423, 526	109, 430, 000 121, 420, 000		60, 129, 853 59, 181, 627

Gold and silver produced at lode mines in Montana in 1942, by counties, in terms of recovered metals

County	Ore sold or treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	County	Ore sold or treated (short tons)	Gold (fine ounces)	Silver (fine ounces)
Beaverhead Broadwater Cascade Deer Lodge Fergus Flathead Granite Jefferson Ludith Basin Lewis and Clark	27, 522 43, 375 77, 208 8, 879 54, 815 27, 879 100, 206 53, 622 36, 724 317, 474	3, 550 11, 479 2, 765 2, 151 1, 749 370 8, 488 7, 180 221 7, 731	59, 563 39, 337 730, 620 5, 971 744 770, 206 584, 415 155, 139 216, 135 297, 083		94 191 25, 175 52, 539 2, 592 50 24, 274 4,753,741 5,678,280	105, 650	270 360 33, 961 38, 783 5, 286 20, 219 8, 123, 781 11,181,181
Lincoln Madison	890 71, 030	25, 471	2, 527 96, 781	Total, 1941	5,642,249	184, 864	12,376,890

Gold and silver produced at placer mines in Montana in 1942, by counties, in fine ounces, in terms of recovered metals

		icing	Drift	min-								
County		l hy- ulic		Drift min- ing		Dry land 1		gline ing 1	Floating bucket		Total	
	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver	Gold	Silver
Beaverhead Broadwater Deer Lodge Fergus	23 1, 722 1 5	3 153			1, 122 29	160 5	113 1,623	10 157			1, 258 3, 374 1	173 315
Granite Jefferson Lewis and Clark Lincoln	63 12 69 41	5 10			623 129	208 21			2, 549 8, 233 14, 252	220 3, 188 1, 395	2, 612 8, 868 14, 450 41	225 3, 396 1, 426
Madison Meagher Mineral	31 62 76	6 7					888	174	1, 934	322	2, 853 62 76	502 7
Missoula Park Powell	29 37 531	8 157			1, 696 75	31			4, 315	615	1, 725 4, 352 606	31 623 166
Ravalli Sanders Silver Bow	4 5 21	7					929	66			933 5 21	766
Total, 1941	2, 732 2, 305	356 353	139	17	3, 674 14, 663	434 2, 408	3, 553 10, 660		31, 283 33, 844		41, 242 61, 611	6, 937 10, 035

<sup>&</sup>lt;sup>1</sup> A floating washing plant supplied with gravel by a dragline excavator is called a "dragline dredge"; a stationary or movable washing plant supplied with gravel by any type of power excavator is called a "dry-land dredge."

# MINING INDUSTRY

Continuous operation of the copper mines at Butte by the Anaconda Copper Mining Co., at the expense of closing the zinc mines, caused the State output of copper to increase; and the closing of the zine mines at Butte caused the production of silver, lead, and zinc to decrease. However, despite this decrease the output of zinc and zinc-lead ore increased in several counties, principally Judith Basin, Lewis and Clark, Beaverhead, and Granite. The widespread closing of gold mines, both lode and placer, resulted in a sharp drop in gold output. Metals from ores treated at amalgamation and cyanidation plants and ore shipped crude to smelters declined in 1942.

Decreases of 20,369 fine ounces in gold and 3,098 fine ounces in silver were noted in the yield from placer mines. Seven connected-bucket floating dredges were active in 1942. They treated 7,539,916 cubic yards of gravel and recovered gold valued at \$1,094,905 indicating an average recoverable gold value of 14.5 cents per cubic yard treated. Dragline and power shovels with both dry-land and floating washing plants were reported in operation at 14 properties. The plants washed 976,651 cubic yards of gravel and recovered gold valued at \$252,945, indicating an average recoverable gold value of 25.9 cents to the cubic yard washed.

#### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

Ore sold or treated in Montana in 1942, with content in terms of recovered metals

Source	Mines pro- ducing	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Dry and siliceous gold ore Dry and siliceous gold-silver ore Dry and siliceous silver ore	180 45 54	77, 231	8, 224	489, 357	199, 954	481, 266	
Copper oreLead oreZinc oreZinc oreZinc-lead oreZinc-lead ore	279 17 84 8 25	2 218, 235	15, 261 2, 368	6, 212, 356	1 276, 498, 651 53, 178 75, 542		42, 193, 000
Total, lode mines Total, placers	³ 370 170	5, 678, 280	105, 650 41, 242	11, 181, 181 6, 937	1 282, 388, 000	40, 100, 000	109, 430, 000
Total, 1941		5, 678, 280 5, 642, 249			1 282, 388, 000 4 256, 072, 000		

Includes 5,327,407 pounds recovered from precipitates.
 Includes 204,362 tons of current slag fumed.
 A mine producing more than 1 class of ore is counted but once in arriving at total for all classes.
 Includes 5,503,555 pounds recovered from precipitates.

# METALLURGIC INDUSTRY

The 5,678,280 tons of ore produced from Montana lode mines in 1942 were treated as follows: 12,773 tons at amalgamation plants, 239,166 tons at cyanidation plants, 4,977,953 tons at concentration mills, 244,026 tons shipped crude to smelters, and 204,362 tons treated

at a slag-fuming plant.

Three cyanidation mills treated 75,730 tons of gold ore, which contained 4,281 ounces of gold and 18,260 ounces of silver; the bullion and precipitates produced yielded 3,603 fine ounces of gold and 14,934 ounces of silver, indicating an average recovery of 84 percent of gold and 82 percent of silver. These three mills reported the consumption of 23,247 pounds of sodium cyanide, 27,070 pounds of calcium cyanide, 11,915 pounds of zinc dust, and 259,780 pounds of lime.

Ore treated at straight concentration plants increased from 4,661,117 tons in 1941 to 4,977,953 tons in 1942. The 1942 total comprised 82,758 tons of siliceous ores, 4,319,953 tons of copper ore, 880 tons of lead ore, 2,491 tons of zinc ore, and 571,871 tons of zinc-lead ore.

The East Helena smelter operated continuously in 1942 and treated ores and concentrates chiefly from Montana and Idaho. conda Copper Mining Co. operated its electrolytic zinc plants at Anaconda and Great Falls throughout 1942. Zinc concentrates were received and treated from most of the Western States but principally from Montana, Idaho, Utah, Washington, Nevada, New Mexico, and California; the concentrates from New Mexico were treated upon a In addition to treatment of concentrates from domestic sources, the Anaconda and Great Falls plants treated over 100,000 tons of zinc concentrates from foreign sources, chiefly upon a toll basis, for the accounts of the Metals Reserve Co., United States Smelting, Refining & Mining Co., and American Zinc Co. foreign concentrates originated at mines in Australia, Canada, Chile, Mexico, and Peru. The Metals Reserve Co. maintains a stock pile of zinc concentrates at Anaconda, which are received into the Anaconda Copper Mining Co. account as smelting capacity permits. Currently the stock pile is equivalent to about a 20-day run. At the beginning of 1942 the plants comprised 4 units at Anaconda and 8 units at Great Falls. During the year the capacity was increased 25 percent, and at the beginning of 1943 the Anaconda section had 5 units and the Great Falls 10 units. As of April 1943, the Anaconda and Great Falls sections combined were producing at the rate of approximately 2,750,000 pounds of slab zinc, dross, and oxide per unit per month. At Anaconda the capacity of the copper concentrator was increased 20 percent—rated now as about 16,000 tons per day—and at the smelter an entirely new converter plant was erected.

Details of the treatment of all ores produced in Montana in 1942 are given in the tables that follow.

Mine production of metals in Montana in 1942, by methods of recovery, in terms of recovered metals

Method of recovery	Material treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Ore amalgamated. Ore and old tailings cyanided. Concentrates smelted 1. Copper precipitates smelted. Ore smelted. Slag tumed. Placer.	12,773 239,166 681,716 4,644 244,026 204,362	956 27, 061 41, 382 36, 251 41, 242	207 66, 202 9, 318, 651 1, 768, 711 27, 410 6, 937	273, 865, 329 5, 327, 407 3, 195, 264	30, 247, 943 5, 987, 057 3, 865, 000	67, 549, 300 1, 500, 700 40, 380, 000
Total, 1941		146, 892 246, 475	11, 188, 118 12, 386, 925	282, 388, 000 256, 072, 000	40, 100, 000 42, 518, 000	109, 430, 000 121, 420, 000

<sup>&</sup>lt;sup>1</sup> Includes zinc concentrates treated at electrolytic plants.

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in Montana in 1942, by types of mills and by counties, in terms of recovered metals

AMALGAMATION MILLS

		Recovered	l in bullion	Con	centrates sr	nelted and	recovered 1	netal
County	Ore treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Concentrates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)
Broadwater	846	324	41					
Granite Jefferson Lewis and Clark	40 210 157	14 72 70	4 22 35	7 4	19 4	145 52	244	1, 786
Madison Park Powell Ravalli	8, 633 2, 747 90 50	116 308 21 31	37 67 1	296 309	1, 451 319	236 146	9,962 900	
Total, 1941	12, 773 99, 482	956 7, 938	207 2, 508	616 2, 200	1, 793 4, 477	579 4, 159	11, 106 11, 180	1, 786 21, 969
		CY	ANIDATI	ON MIL	LS			
Beaverhead Broadwater Deer Lodge	11,000 32,885 8,252 54,804	2, 949 2, 985 2, 053 1, 743	432 977 1,039 741	3, 304	4,718	892	2,000	
Fergus Granite Lewis and Clark Madison	3, 038 34, 721 39, 900	61 4, 417 7, 066	37 21, 709 3, 139	256	2, 892	1, 432		
Phillips Silver Bow	52, 466 2, 100	5, 075 712	38, 052 76					
Total, 1941	239, 166 443, 388	27, 061 56, 293	66, 202 166, 587	3, 560 143	7, 610 1, 888	2, 324 815	2,000 1,156	22, 550
Grand total: 1942 1941	251, 939 542, 870	28, 017 64, 231	66, 409 169, 095	4, 176 2, 343	9, 403 6, 365	2, 903 4, 974	13, 106 12, 336	1, 786 44, 519

Mine production of metals from concentrating mills in Montana in 1942, by counties, in terms of recovered metals

			Concer	itrates smel	ted and recov	ered metal	
County	Ore treated (short tons)	Concentrates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Broadwater	6, 172	1, 375	1, 234	7, 199	8, 941	99, 685	165, 600
Cascade	77, 083	4, 273	2, 524	682, 001	29, 747	2, 034, 462	1, 018, 700
Granite	24, 906	2, 483	. 56	80, 068	52, 193	1, 085, 797	1, 452, 000
Jefferson	28, 893	2, 445	306	74, 524	46, 561	918, 347	1, 185, 000
Judith Basin	36, 516	4,943	135	215, 208	107, 415	3, 406, 860	1, 751, 000
Lewis and Clark	65, 102	7, 535	556	223, 838	702, 326	4, 632, 165	2, 536, 000
Lincoln	890	103	64	2, 527		114, 300	2, 550, 550
Madison	4,727	560	1,276	2,659	36, 788	6, 520	5, 300
Mineral	94	45		270		12,000	18,700
Park	22, 309	967	4,845	29, 041	147, 100	107, 900	95, 000
Powell	573	28	3	1,628	164	22, 078	
Sanders	23, 552	3,060	47	17, 370	19, 910	3, 395, 043	696, 000
Silver Bow	4, 687, 136	649, 723	20, 933	7, 979, 415	272, 701, 078	14, 411, 000	58, 626, 000
	4, 977, 953	677, 540	31, 979	9, 315, 748	273, 852, 223	30, 246, 157	67, 549, 300
Total, 1941	4, 661, 117	660, 251	53, 681		247, 693, 040	29, 468, 528	83, 918, 000

# Gross metal content of concentrates produced from ore mined in Montana in 1942, by classes of concentrates smelted

	Concen-		Gre	oss metal con	tent	
Class of concentrates	trates (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Dry gold Dry silver Copper Lead Lead Lead-copper Zine. Zine-lead Dry iron (from zine-lead ore)_	5, 194 1, 142 556, 914 15, 648 4, 979 60, 385 15, 810 21, 644	10, 586 2, 169 21, 034 1, 414 461 3, 669 764 1, 285	3, 137 357, 244 6, 179, 917 894, 522 212, 013 1, 245, 299 251, 842 174, 677	15, 626 17, 077 273, 256, 772 1, 080, 903 670, 537 1, 940, 500 279, 563 336, 598	103, 088 18, 345, 488 5, 068, 261 5, 189, 037 3, 278, 410 582, 975	1, 859, 659 583, 171 59, 532, 263 15, 536, 827 1, 689, 997
Total, 1941	681, 716 662, 594	41, 382 60, 046	9, 318, 651 10, 102, 389	277, 597, 576 252, 652, 104	32, 567, 259 32, 047, 952	79, 201, 917 97, 392, 428

# Mine production of metals from Montana concentrates shipped to smelters in 1942, in terms of recovered metals

#### BY COUNTIES

	Concen- trates (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)
Broadwater	4,679 4,273 2,483 2,452 4,943 7,539 103 1,112 45 1,276 28 3,060 649,723	5, 952 2, 524 56 325 135 560 64 5, 619 5, 164 27 20, 933	8, 091 682, 001 80, 068 74, 669 215, 208 223, 890 2, 527 4, 327 270 29, 187 1, 628 17, 370 7, 979, 415	10, 941 29, 747 52, 193 46, 805 107, 415 702, 326 46, 750 148, 000 164 19, 910 272, 701, 078	99, 685 2, 034, 462 1, 085, 797 920, 133 3, 406, 860 4, 632, 165 114, 300 6, 520 12, 000 107, 900 22, 078 33, 95, 043 14, 411, 000	165, 600 1, 018, 700 1, 452, 000 1, 185, 000 1, 751, 000 2, 536, 000 18, 700 95, 000
Total, 1941	681, 716 662, 594	41, 382 60, 046	9, 318, 651 10, 102, 389	273, 865, 329 247, 705, 376	30, 247, 943 29, 513, 047	58, 626, 000 67, 549, 300 83, 918, 000

Mine production of metals from Montana concentrates shipped to smelters in 1942, in terms of recovered metals—Continued

#### BY CLASSES OF CONCENTRATES

	Concen- trates (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)
Dry gold	5, 194 1, 142 556, 914 15, 648 4, 979 60, 385 15, 810 21, 644	10, 586 2, 169 21, 034 1, 414 461 3, 669 764 1, 285	3, 137 357, 244 6, 179, 917 894, 522 212, 013 1, 245, 299 251, 842 174, 677	14, 287 14, 347 269, 915, 706 918, 141 569, 841 1, 840, 958 265, 585 326, 464	98, 964 17, 601, 986 4, 865, 507 4, 694, 831 2, 983, 348 3, 307	53, 566, 000 13, 983, 300
	681,716	41, 382	9, 318, 651	273, 865, 329	30, 247, 943	67, 549, 300

Gross metal content of Montana crude ore shipped to smelters in 1942, by classes of ore

	0 (-1	Gross metal content							
Class of ore	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)			
Dry and siliceous gold	39, 328 75, 081 84, 418 18, 761 15, 056 11, 382	24, 778 7, 814 1, 093 195 2, 310 61	87, 581 462, 819 988, 073 40, 321 178, 748 11, 169	36, 182 188, 292 1, 757, 844 1, 460, 017 62, 019 89, 166	97, 381 537, 483 280, 346 4, 560, 090 874, 432	2, 382, 29			
Total, 1941	244, 026 267, 670	36, 251 60, 587	1, 768, 711 2, 105, 406	3, 593, 520 3, 112, 577	6, 349, 732 10, 570, 644	2, 382, 29			

Mine production of metals from Montana crude ore shipped to smelters in 1942, in terms of recovered metals

#### BY COUNTIES

	<u> </u>	BY COUN	TIES			<u> </u>
	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)
BeaverheadBroadwater	16, 522 3, 472	601 2, 218	59, 131 30, 228	106, 000 16, 059	1, 578, 700 601, 015	1, 500, 700
Cascade Deer Lodge Fergus		241 98 6	48, 619 4, 932 3	2, 253 3, 000	32, 538	
Flathead Granite Jefferson	27, 879	370 8, 357 6, 783	770, 206 504, 306 80, 448	101, 000 175, 807 42, 195	1, 227, 700 229, 803 573, 167	
Judith Basin Lewis and Clark Madison	208 13, 132 17, 770	2, 684 12, 670	927 24, 039 89, 278	7, 585 40, 674 26, 250	326, 835 787, 780	
MissoulaParkPhillips	191 119	282 75 151	360 4, 707 731	700	18, 200	
Powell Sanders Silver Bow	1, 929 722 64, 505	835 79 715	3, 657 2, 849 144, 290	1, 136 3, 090 2, 669, 515	8, 622 602, 557	
Total, 1941	244, 026 267, 670	36, 251 60, 587	1, 768, 711 2, 105, 406	3, 195, 264 2, 863, 039	5, 987, 057 9, 950, 953	1, 500, 700
		CLASSES		2,000,000	0,000,000	
Des and cities are noted	20, 200	04 850	07 701	00.100	00.101	<u> </u>
Dry and siliceous gold Dry and siliceous gold-silver	39, 328 75, 081	24, 778 7, 814	87, 581 462, 819	33, 160 181, 428	93, 161 428, 825	
Dry and siliceous silver Copper	84, 418 18, 761	1, 093 195	988, 073 40, 321	1, 417, 119 1, 443, 229	238, 401	
LeadZinc	15, 761 15, 056 11, 382	2, 310 61	178, 748 11, 169	53, 178 67, 150	4, 367, 969 858, 701	1, 500, 700
	244, 026	36, 251	1, 768, 711	3, 195, 264	5, 987, 057	1, 500, 700

# REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, lead, and zinc in Montana in 1942, by counties and districts, in terms of recovered metals

County and district		produc- ig	Ore sold or treated	Gold	d (fine oun	œs)	Silve	r (fine ou	ices)	Copper (pounds)	Lead (pounds)	Zinc (pounds)	Total value
Councy and district	Lode	Placer	(short tons)	Lode	Placer	Total	Lode	Placer	Total	(pounds)	(podnas)	(pounds)	Valuo
Beaverhead County: Argenta Bannack Big Hole	1	6	13, 060 45	3, 300 57	159 6	3,300 216 6	13, 244 90	31 1	13, 244 121 1	6, 000 1, 800	440, 600		\$155, 164 7, 864 211
Blue Wing Bryant Elkhorn Horse Prairie Medicine Lodge Viond	2 3 1 1 1	3	20 12, 946 57 284 129 981	133 4 13	1, 093	133 4 1, 106	540 26,474 519 1,693 225 16,778	141	540 26, 474 519 1, 834 225 16, 778	95, 700 1, 900 200 200 200	929, 400 1, 000 172, 700 34, 400 600		384 236, 896 806 51, 609 2, 489 13, 500
Broadwater County: Backer Beaver Cedar Plains Park or Indian Creek	3 9 9	5 3 11	121 2, 684 39, 011 1, 559	173 1, 417 8, 775 1, 114	50 4 3,320	223 1, 417 8, 779 4, 434	104 30, 091 5, 535 3, 607	308	111 30, 091 5, 535 3, 915	22, 700 4, 000 300	300 467, 600 170, 000 62, 800	165, 600	7, 904 120, 470 323, 075 162, 218
Cascade County: Montana Unorganized (Barker) Deer Lodge County:	. 1		77, 094 114	2, 765		2,765	730, 101 519		730, 101 519	32,000	2, 049, 300 17, 700	977, 400 41, 300	848, 031 5, 396
Dry Gulch Georgetown Oro Fino Fergus County:	3 2	1	8, 361 518	2, 141 10		2, 141 10	1, 156 4, 815		1, 156 4, 815	2,000 1,000			75, 999 3, 895
Cone Butte	. 1	1 1	54, 804 27, 879	1,743 370	3 2	1, 746 2 370	741 770, 206		770, 206	101,000	1, 227, 700		61, 637 70 655, 129
Granite County: Boulder Dunkleberg First Chance Flint Creek	5 3 5	7	648 22,507 583 75,908	731 18 329 6,900	3 2,599	734 18 2, 928 6, 900	1, 336 54, 824 346 526, 275	225	1, 336 54, 824 571 526, 275	7,700 44,100 175,900	1, 600 1, 052, 400 238, 600	17, 300 1, 149, 400 285, 300	29, 288 222, 357 102, 886 679, 543
Gold CreekHendersonMaxvilleRed Lion	1 1 2 2		3 59 80 127	1 1 10 61		1 1 10 61	38 1,094 457 7		38 1,094 457 7 38	300	1, 000 22, 000		129 849 2, 149 2, 140 15, 392
Rock Creek		1 1	291	437	2 8	439 8	38		38				15, 392

Jefferson County:		1 1						i i		1	- 1		
Amazon	3	l	152	10		10	841		841	1, 200	10,600		1, 803
Big Foot	2		46	28		28	464		464		10,000	3, 300	2, 287
Boulder	Ī		6				218		218				155
Cataract	15	1	2, 210	553	5	558	27, 104		27, 104	30, 700	52, 600		46, 043
Clancey	2	2	27	6	8, 688	8,694	246	3, 358	3, 604		3, 400		307, 081
Colorado	8	I	31, 982	829		829	102, 060		102, 060	49, 700	1, 160, 000	1, 176, 700	294, 758
Elkhorn	6		2,036	70		70	13, 701		13, 701	1, 300	77, 700		17, 556
Golconda	2		6	1		1	69		69		77, 700 © 600		124
Homestake	1		7	2		2	45		45				102
Lowland	1		246	8		8	3, 337		3, 337	2,700			2, 980
McClellan Creek	4		215	99		99	374		374	300			3, 767
Mitchell	1		4	1		1	3		3				37
Montana City	<b>-</b>	4			171	171		38	38				6, 012
Pipestone	1	1	3	2	4	6	3		3				212
Warm Springs	2		77	72		72	329		329	300	1,600	5,000	3, 362
Whitehall	10		16, 308	4, 667		4, 667	4, 929		4, 929	1,000	160, 400		177, 718
Wilson and Ticer Creeks	1		297	832		832	1, 416		1, 416	1,800	16, 400		31, 444
Judith Basin County:			1.5										F04 00F
Barker	2		36, 526	137		137	215, 235		215, 235	107, 700	3, 407, 000	1, 751, 000	561, 995
Yogo	1		198	84		84	900		900	7, 300			4, 463
Lewis and Clark County:					100								
Blue Cloud	1		9				59		59		1,700		156
Dry Gulch	3	1	10, 174	1,656	2	1,658	1,710		1,710				59, 246
Greenhorn		. 2			26	26							910
Heddleston	2		62, 938	146		146	197, 259		197, 259	683, 800	4, 579, 600	2, 532, 000	770, 432
Helena	6	13	120	116	7, 387	7, 503	239	682	921		3,000		263, 461
Lincoln	1	4	3		136	136	14	24	38		300		4, 807
Marysville	12		24, 155	4, 085		4, 085	21, 264		21, 264	4, 300	54, 700	4,000	162, 653
Missouri River		. 1			6,884	6,884		713	713				241, 447
Ophir Gulch	1		20	55		55	17		17	700			2, 022
Rimini	12	1	993	162	7	169	10,845	7	10, 852	1,800	115, 300		21, 575
Scratch Gravel	4.		2, 622	184		184	4,050		4,050	1,100	77, 400		14, 639
Smelter	2		210, 345	15		15	30, 098		30, 098	36, 100	3, 976, 900	40, 380, 000	4, 048, 088
Stemple-Gould	6	3	6, 092	1,312	8	1, 320	31, 507		31, 507	15, 200	14, 700 400		71, 429
Wolf Creek	1		3				21		- 21		400		42
Lincoln County:			000		00		0 507	1	0. 507		114, 300		12, 745
Libby	2	6	890	64	30	94	2, 527		2, 527		114, 500		12, 745
Troy		·  1			3	8							280
		1			8	8							200
Madison County:			370	00		96	4, 365	1	4, 365	300	220, 700		21, 287
McCarthy Mountain Norris and Norwegian	2 14		14, 765	96 7, 323	491	7, 814	4, 649	59	4, 708	100	220, 100		276, 850
Pony and South Boulder	14	2	4, 863	1, 323	491	1, 398	2, 693	00	2, 693	36, 700			55, 286
Renova	5		10. 564	9, 818		9, 818	60, 871		60, 871	700			387, 001
Rochester.	14		1, 280	284		284	5, 656		5, 656	11, 300	194,000		28, 327
Sand Creek			1, 200	204		1 204	0,000		0,000	11,000	154, 000		35
Sheridan	1 13	i	2, 737	515	8	523	8, 429		8, 429	6, 700	278, 000		43, 736
Silver Star	8	1	35, 531	5, 410	•	5, 410	3, 600		3, 600	16, 900	57, 600	5, 300	198, 307
Tidal Wave	9		30, 331	215		215	1, 073		1, 073	10, 900	42, 300	0, 300	11, 134
Virginia City	14	9	684	371	908	1, 279	5. 341	180	5. 521	200	72, 000		48, 715
Washington	3		38	40	1, 446	1, 486	104	263	367	200	1 700		52, 385
AA SEUMÉTOR	1 3	2	38	40	1, 440	1,400	104	1 200 1	007		1, 100	l	1 02,000

Mine production of gold, silver, copper, lead, and zinc in Montana in 1942, by counties and districts, in terms of recovered metals—Continued

County and district		produc- ng	Ore sold or treated	Gol	d (fine oun	ces)	Silve	r (fine ou	inces)	Copper	Lead	Zinc	Total
	Lode	Placer	(short tons)	Lode	Placer	Total	Lode	Placer	Total	(pounds)	(pounds)	(pounds)	value
Meagher County:													40.45
Beaver and Thomas	-	6			62	62		7	7				\$2, 178
Cedar and Trout		19			76	76					l		2, 660
Iron Mountain			94				270		270		12,000	18, 700	2, 73
Missoula County:	3		172	281	i l	281	291	5.7	291		5.0		10.046
Coloma Elk Creek			172	201		281	291		291				10, 042
Nine Mile		6			1,724	1, 724		31	31				60, 362
Wallace	1		19	1		1	69		69	700			169
Park County:	1				4 250	4 950		623	400				150 500
Emigrant New World		9	22, 376	4, 847	4, 352	4, 352 4, 847	33, 743	023	623 33, 743	147, 100	126, 100	95,000	152, 763 228, 723
Sheepeater	í		2,799	700		700	218		218	900	120, 100	80,000	24, 764
Phillips County: Little Rockies	2		52, 539	5, 226		5, 226	38, 783		38, 783				210, 489
Powell County:													
Big Blackfoot		3	16	16	346 102	362 102	28	131 14	159 14		300		12, 803 3, 580
Nigger Hill	5	3	624	35	6	41	2, 098	1.4	2, 098	1,300	28,000		4, 960
Ophir Gulch	_1 1	Š	i	ĩ	45	46	2,000	7	2,007	1,000	20,000		1,615
Pioneer		5			107	107		14	14				3, 755
Yourname Creek	1 5		91 1,860	28 779		28 779	3, 157		0 157		2,400		982 29, 671
Ravalli County: Overwich	- 1	3	50	31	933	964	0, 107	66	3, 157 66		2, 400		33, 787
Sanders County:	1		"	. 01	000	001			00				00, 10.
Eagle	. 1		23, 195	38		38	20, 025		20, 025	17,000	3, 997, 600	696, 000	350, 194
Plains	. 1		10				14		14	1,700			210
Revais Creek Vermillion	1 1		800 269	12 76	5	12 81	83 97		83 97	4, 300			999 2, 904
Silver Bow County:	1 1	1	205	10	, °	01	91		9,				2, 80
Divide Creek			9	4	l	4	45		45				172
German Gulch	-	1			10	10		4	_4				353
Highland Lost Child	. 1		2, 100	712	2	712	76		76				24, 974 70
Melrose	1	1 1	19		2	2	329		329	200			328
Summit Valley	25	7	4, 751, 613	21, 644	7	21, 651	8, 123, 331	3	8, 123, 334	280, 697, 800	14, 411, 000	58, 626, 000	46, 916, 567
Total Montana	370	170	5, 678, 280	105, 650	41, 242	146, 892	11, 181, 181	6, 937	11, 188, 118	282, 388, 000	40, 100, 000	109, 430, 000	60, 129, 858

#### BEAVERHEAD COUNTY

Argenta district.—The Ermont Mines, Inc., was again the chief gold producer in the Argenta district. In 1942 the company operated its 100-ton countercurrent cyanide mill until about October 15, when all work stopped. During the 9½ months of activity the mill treated about 11,000 tons of gold ore, equivalent to about one-third of that treated in 1941. The decreased output of ore was due to a shortage of miners. Virtually all the remainder of the district output was lead ore.

Bannack district.—Placer gravels in 1942 continued to be the chief source of gold in the Bannack district. The Ralph E. Davis Syndicate operated its dragline dredge at the Grasshopper Creek placer until May 11, and the Traderhorn Mining & Construction Co. operated its

dry-land dredge at the Rimrock placer until April 30.

Bryant district.—A total of 12,863 tons of siliceous tailings, crude lead ore, and old zinc slag was shipped direct to Utah smelters from the Hecla and Greenwood mines in 1942 by L. D. Foreman. Most of the 12,863 tons shipped was old zinc slag (11,382 tons) from the Hecla slag dump and contained about 2.5 percent lead and 10 percent zinc, in addition to the other usual lead blast-furnace slag constituents. The slag was shipped to Tooele and there treated first in the lead blast furnace, followed by treatment in the slag-fuming plant. The remaining production from the district was copper ore shipped crude to Washoe.

Horse Prairie (Colorado) district.—Virtually all the placer output from the Horse Prairie district in 1942 came from the Chinatown property of Associated Placers, Inc., on Colorado and Jeff Davis Creeks and the Golden Leaf property of W. C. McLeod on Jeff Davis Creek. Both operators used dry-land dredges and washed a total of 106,000 cubic yards of gravel. Hoffman & Steele shipped 284 tons of lead ore in 1942 to Midvale (Utah) from the H. & S. mine.

Vipond district.—Most of the production from the Vipond district in 1942 was silver ore shipped to Washoe from the Lone Pine &

Argyle property.

#### BROADWATER COUNTY

Backer district.—The Superior mine was the chief source of lode gold; its output comprised gold ore shipped direct to a smelter and gold ore amalgamated. Most of the placer output came from a dryland dredge operated in Confederate Gulch by R. G. Woodard.

Beaver district.—The value of the metal production from the Beaver district in 1942 was much lower than in 1941 because the output of gold ore was smaller. Lead ore and zinc-lead ore, both rich in gold, were shipped from the East Pacific and East Pacific Tunnel No. 4 to East Helena and Anaconda zinc concentrator, respectively, and gold ore from the Vosburg property was shipped crude to East Helena. The remainder of the lode output was crude ore shipped direct to smelters and was chiefly gold ore from the Edna No. 2, Custer Group, Iron Age, and Martha Washington properties.

Cedar Plains district.—The M & M Mining Co. was again the leading producer in the district and treated 32,000 tons of gold ore from the Ohio Keating mine in its 100-ton cyanidation-concentration mill. The property, unlike most other gold properties in Broadwater County, was active throughout 1942 and is still active in 1943. The

C. G. Gold Corporation operated the Keating mine and its 100-ton flotation concentrator until May 1, 1942, when all work ceased for the

duration of the war.

Park district.—The most important lode producer in the Park district was again the Marietta mine, from which gold ore (112 tons) and lead ore (269 tons) were shipped direct to smelters. The output from placer operations continued to be the chief source of gold in the district, but it was less than half that produced in 1941. A. R. Douglas, the outstanding producer in the district, operated a dry-land dredge on Indian Creek until September, when all activity ceased. The Cooley Gravel Co., formerly the chief producer in the district, operated until October 14, when all work ceased.

#### CASCADE COUNTY

Montana district.—The Montana district reported a substantial decrease in output of gold, silver, lead, and zinc in 1942 compared Zinc-lead ore from the Broadwater group treated by the Klies Mining Co. in its 80-ton flotation mill amounted to 23,783 tons compared with 29,190 tons in 1941. The ore treated in 1942 had a higher silver and gold content but a lower zinc and lead content, which explained most of the decrease in the zinc and lead output of the district. In addition to ore from the Broadwater group, the company milled 5.082 tons of silver-lead ore from the Graham and Hollowbush The latter group was closed indefinitely on December 31. Silver ore milled by the Lexington Mining Co. from the Big Seven Group represented nearly half of the silver output of the district. In 1942 the company treated about 22,000 tons of silver ore compared with 32,718 tons in 1941 in its 100-ton flotation mill and made highgrade silver concentrates. In addition, 74 tons of lead ore rich in silver were shipped direct to East Helena. The Florence Co. operated the Florence mine throughout 1942 but closed its mill in September; the remainder of the year was spent developing the mine. During the period of operation about 11,000 tons of silver ore were milled in the company 75-ton flotation mill, making lead concentrates. Silver ore from the Star group was treated in the New London Mining Corporation 40-ton flotation mill, making lead concentrates. The Queen Leasing Co. operated the Queen of the Hills mines through March, when the property was closed. The 60-ton flotation mill was dismantled and moved from the property.

#### DEER LODGE COUNTY

Georgetown district.—The Sentinel Mines, Inc., operated the Holdfast-Southern Cross group from January until August, when all activity stopped. During this period 8,252 tons of gold ore were treated in the company 65-ton countercurrent cyanidation mill, yielding 2,053 ounces of gold and 1,037 ounces of silver.

#### FERGUS COUNTY

North Moccasin district.—The North Moccasin Mines Syndicate operated its Barnes-King open-cut mine throughout 1942 and treated 54,804 tons of gold ore by cyanidation compared with 75,535 tons in 1941. Gold occurs in porphyry, limestone, and clays, which are carried to the cyanide mill on a conveyor belt and leached.

#### FLATHEAD COUNTY

Hog Heaven district.—The Anaconda Copper Mining Co. operated its Flathead mine throughout 1942, although the rate of output declined considerably during the latter part of 1942. During the year the company shipped 23,024 tons of highly siliceous silver ore crude to Washoe and 4,395 tons of lead ore crude to East Helena. The West Flathead, also owned and operated by the Anaconda Copper Mining Co., produced 448 tons of high-grade silver ore, all of which was shipped direct to Washoe.

#### GRANITE COUNTY

Boulder district.—High-grade gold ore from the Gold King and Gold Mountain mine was shipped crude to East Helena in 1942 and repre-

sented most of the district output.

Dunkleberg district.—Virtually all of the output of the Dunkleberg district in 1942 was zinc-lead ore from the Forest Rose and Wasa mines, both operated by the Forest Rose Syndicate. The Wasa properties are under lease to the Forest Rose Syndicate and are contiguous to the Forest Rose mine. According to the Forest Rose Syndicate, work was started on the Wasa and Monarch properties in 1942, and considerable fine oxide cappings underlaid by sulfide ores were investigated at shallow depth. This work is promising, showing as much as 12-foot widths of fair-grade zinc-lead ore. Roads have been built to connect the properties. An aggregate of 22,500 tons of zinclead ore (Forest Rose and Wasa mines), which averaged about 4 percent zinc and 4 percent lead, was treated in 1942 in the Forest Rose The output of zinc and lead concentrates pro-100-ton flotation mill. duced was nearly double that in 1941.

First Chance district.—Most of the placer gold output in 1942 was

recovered from the floating connected-bucket dredge of the Star Pointer Exploration Co., which operated in Bear Gulch. pany operated its electrically powered Yuba dredge from January through October and handled 1,308,700 cubic yards of gravel. Crude gold ore shipped direct to smelters comprised the output from lode mines and came principally from lessee operations on the Mitchell-Mussigbrod and Grant and Hartford groups.

Flint Creek district.—Old tailings from the Granite-Bimetallic mine continued to be the chief source of metal output from the Flint Creek, In 1942 the Philipsburg Mining Co., operator of the mine, shipped over 66,000 tons of these tailings direct to the Tacoma. Washoe, and East Helena smelters, for flux. The Moorlight Mining Co. operated the True Fissure mine and shipped crude lead and silver ore direct to East Helena and Washoe, respectively, and zinc ore to the Anaconda zinc concentrator. The Marie Leasing Co. operated the Marie mine throughout 1942 and shipped 68 tons of crude lead ore and 1,080 tons of rich silver ore direct to smelters; the ore was extracted concurrently with the mining of manganese ore. Manganeseore tailings from the Trout mine, which contained gold and silver, were cyanided in a 50-ton cyanide plant; operations were suspended in July.

Rock Creek district.—The only lode production in the Rock Creek

district in 1942 was from the MacDonald (Ella) mine.

#### JEFFERSON COUNTY

Cataract district.—The Basin Montana Tunnel Co., although inactive itself in 1942, granted leases for the purpose of cleaning up the Comet 200-ton flotation mill and shipping ore from the Grey Eagle dump. These lessees shipped a total of 793 tons of gold-silver ore and were the largest producers in the district. Other production included crude gold-silver ore from the Crystal, Hope, and Morning

Glory mines and lead ore from the Crescent mine.

Clancey district.—Winston Bros. Co. operated its 6-cubic foot electrically driven Yuba bucket dredge in 1942 from January 14 to October 15, when all work was suspended. During the period of operation the bucket dredge washed 1,520,042 cubic yards of gold-bearing gravel compared with 2,157,277 in 1941. The company was again the largest producer of placer gold in Montana. The remainder of the placer output came from operation of a dry-land dredge on

Clancey Creek by Jefferson Placers.

Colorado district.—The value of the metal output from the Colorado district in 1942 increased compared with 1941 because of much larger output of base metals. The Monongahela-Mount Washington Mining Co. started operations on its Mount Washington property April 7 and continued the rest of the year. During the operating period, 28,799 tons of zinc-lead ore were treated in the company 150-ton flotation mill, resulting in the production of 1,050 tons of lead concentrates and 1,350 tons of zinc concentrates. The lead concentrates were smelted at East Helena, Mont., and the zinc concentrates at Amarillo, Tex. In addition to the zinc-lead ore milled, the company shipped 329 tons of crude lead ore to East Helena, and a lessee shipped 252 tons from the Mount Washington dump. The company, although active for only 9 months in 1942, was one of the major producers of lead and zinc in the State.

Elkhorn district.—Most of the output from the Elkhorn district in 1942 came from the Elkhorn mine, from which 1,720 tons of silver

dump ore were shipped to a smelter.

Montana City district.—Two dry-land dredges treated a total of 10,943 cubic yards of gold-bearing gravel (recovering 168 ounces of gold and 38 ounces of silver) and supplied nearly all the district output in 1942.

Whitehall district.—A lessee operated the Golden Sunlight mine, which was again by far the largest producer in the district, and shipped

over 15,000 tons of gold ore crude to Washoe.

Wilson Creek district.—Gold ore shipped crude to a smelter and gold ore amalgamated and concentrated from the Callahan group (Deer Horn) comprised the only output from the Wilson Creek district in 1942.

## JUDITH BASIN COUNTY

Barker district.—Virtually all the output of the Barker district in 1942 was derived from the zinc-lead ores of the Block P group, operated by the St. Joseph Lead Co. Rehabilitation work on the Block P mine and 400-ton flotation mill was begun in 1941, and by early 1942 the work was completed and actual mining and milling operations started. During the year the mill treated over 36,000 tons of zinc-lead ore, making about 2,900 tons of lead concentrates and about 2,000 tons of zinc concentrates.

一十五日最終をよりの世上の最近の

#### LEWIS AND CLARK COUNTY

Dry Gulch district.—The Golden Messenger Corporation operated its Golden Messenger mine until March, treated about 10,000 tons of ore by cyanidation, and recovered 1,446 ounces of gold and 1,568 ounces of silver.

Heddleston district.—The Mike Horse Mining & Milling Co. operated the Mike Horse mine and its flotation mill throughout 1942 and more than doubled the 1941 output of zinc and copper, while the output of lead was increased substantially. The company increased its milling capacity from 150 tons a day to 200 tons and treated nearly 63,000 tons of zinc-lead-copper ore, which made about 4,500 tons of lead-copper concentrates and about 2,800 tons of zinc concentrates. The

mill was operated three shifts a day 7 days a week.

Helena district.—Porter Bros. Corporation operated its 6-cubic foot Yuba dredge in 1942 from January 1 to October 18, when work was suspended temporarily. On December 8 the dredge was again active and remained in operation the rest of the year. A total of 1,455,393 cubic yards of gravel was washed in 1942 compared with 1,864,078 in 1941, supplying nearly all the placer gold output in the Helena district. Lode production came from several small mines, including the Court House, Spring Hill, and Whitlatch.

Lincoln district.—The Missoula Lincoln Metals Co. operated a dry-land dredge on the Blue Bird placers from June 1 to August 1 and produced nearly all the placer output of the district in 1942. Crude silver ore from the Silver Egal mine was shipped to East

Helena.

Marysville district.—The Martin Mining Co. continued to be the most important producer in the district and in 1942 treated 17,888 tons of old tailings in its 120-ton cyanidation mill. The tailings were mined from the Eck, Brown, and Chevalier ranches by power shovel, hauled to the cyanidation mill, and there roasted, crushed, and cyanided and the gold and silver precipitated. All work was suspended October 5. The Montana Rainbow Mining Co. and individual lessees operated the Drumlummon mine. The production in 1942 comprised 2,117 tons of gold ore, which contained 880 ounces of gold and 3,460 ounces of silver and was shipped crude to East Helena. The company also moved a 160-ton flotation-amalgamation mill from near Libby to the property. The Silver Crescent, Inc., operated the Belmont mine from March 1 to September 5; during this time the company treated 2,594 tons of ore in the 60-ton Drumlummon cyanide mill, which was remodeled in 1941. The company also shipped 177 tons of gold ore crude to East Helena. H. E. Luderer treated gold-silver ore in a 35-ton flotation mill and made 112 tons of lead concentrates, which were shipped to East Helena.

Missouri River district.—The Perry-Schroeder Mining Co. operated its 6-cubic foot Yuba dredge on the Missouri River, 15 miles north of Helena, throughout 1942 and washed 1,869,500 cubic yards of gold-bearing gravel. No platinum was reported recovered in 1942

from this operation.

Rimini district.—The South Dakota Mining Associates acquired control of a large number of mines, dumps, and prospects in the Rimini district in 1942 and shipped test lots of siliceous and lead ore from many of the properties, the more productive being the Bunker Hill, Evergreen, Free Speech, Lexington, Mineral Deposit, and

Transit claims. The aggregate production was 354 tons of lead ore and 268 tons of siliceous gold-silver ore.

Scratch Gravel district.—Most of the output from the Scratch Gravel district in 1942 was siliceous dump ore from the Helena mine dump

shipped crude to East Helena.

Smelter district.—The slag-fuming plant at East Helena, owned and operated by the Anaconda Copper Mining Co., was active throughout 1942, and the output of zinc-lead fume was considerably greater than in 1941. The company treated 204,362 tons of current slag and old slag from the East Helena lead smelter and produced zinc-lead fume valued at approximately \$4,025,000. The American Smelting & Refining Co. re-treated about 5,900 tons of gold-silver-lead-copper

slag in 1942.

Stemple district.—The Gould mine, operated by the Standard Silver-Lead Mining Co., was again the leading producer in the district in 1942, although all work was suspended March 1. During the first 2 months of the year the company treated 4,239 tons of gold ore in its 100-ton cyanidation mill and recovered 714 ounces of gold and 5,078 ounces of silver from bullion shipped to the mint. The company also shipped several tons of crude gold ore and some rich cleanings to East Helena. The Swan Sea Mines, Inc., treated about 1,500 tons of gold-silver ore in a concentrating mill, making 120 tons of lead-copper concentrates, which were shipped to East Helena.

# LINCOLN COUNTY

Libby district.—Most of the lode output in the Libby district in 1942 came from the Snowshoe group of properties, operated by Snowshoe Mines & Co. The company operated the property from April 12 to November 9 and treated about 880 tons of lead ore in its 60-ton flotation mill, making 102 tons of lead concentrates.

#### MADISON COUNTY

McCarthy Mountain district.—Mueller Bros. operated the B. B. & I. E. property throughout 1942 and shipped 349 tons of silver-lead ore crude to East Helena; the remainder of the district output was a test lot of gold ore shipped crude to Washoe and a little gold ore

amalgamated from the Hidden Treasure mine.

Norris district.—The Boaz mine operated its 50-ton cyanide-concentration mill all of 1942 on company and custom ore. On company account 13,349 tons of ore were treated, yielding 3,719 fine ounces of gold and 2,089 ounces of silver in bullion and 255 tons of gold concentrates containing 2,882 ounces of gold and 1,420 ounces of silver. Grubstake mine shipped 111 tons of crude gold ore, which contained 293 ounces of gold, to Washoe and 5 tons of gold ore for treatment at the Boaz mill; this property was the second-largest producer in the The Montana Coal & Iron Co. operated the Goldistrict in 1942. conda mine from January 1 to June 23 and shipped crude gold ore to Washoe; after June, all equipment was removed and the property was abandoned. Other producers included the Red Bluff, Madisonian dump, and Heleene mine. Homer Wilson operated a floating connected-bucket dredge (5-cubic foot Yuba) on the Norwegian Placer claim from May to September 8 and washed 265,000 cubic yards of gravel, recovering 489 fine ounces of gold and 59 ounces of cilver.

Pony district.—Gold ore from the Mammouth mine, which was operated all year by the Liberty Montana Mines Co., continued to be the chief source of metal in the district. The company treated 4,687 tons (17,585 in 1941) in its 120-ton flotation-gravity concentration mill, making 28 tons of gold concentrates and 514 tons of copper concentrates.

Renova district.—The West Mayflower mine, owned and operated by the Anaconda Copper Mining Co., was by far the largest producer in the district, and in 1942 the company shipped to Washoe 10,367 tons of ore, which contained 9,670 ounces of gold and 60,688 ounces

of silver.

Rochester (Rabbit) district.—Gold ore from the Thistle mine, lead ore from the Jack Rabbit mine, and copper ore from the Ellen Marshall mine, all shipped crude to smelters, comprised most of the output

from the Rochester district in 1942.

Sheridan district.—The Sheridan Gold Mining & Milling Co. remained the largest producer in the Sheridan district in 1942 and operated the Toledo group and Uncle Sam mine. The Toledo group was active during the first 10 months of 1942; then Victoria Mines, Inc., Silverstar, Mont., took over the lease and option held by the Sheridan Gold Mining & Milling Co. During the period of activity at the Toledo group, 1,673 tons of high-grade lead ore and 326 tons of gold ore were shipped crude to smelters; the Uncle Sam mine produced 98 tons of crude gold ore. The Standard Silver Lead Mining Co. operated the Buckeye mine and shipped 497 tons of gold-silver ore to a smelter. Several other small lode mines were active in 1942; most of them shipped crude gold ore to smelters.

Silver Star district.—The Victoria Mines, Inc., was the chief producer in the district in 1942 and treated about 26,000 tons of gold ore in its 125-ton cyanidation mill; in addition, the company shipped 398 tons of rich crude gold-lead ore to East Helena and 476 tons of gold ore to Washoe. The cyanide mill was closed in the fall of 1942 but is expected to reopen to treat base-metal ores from the Toledo group of properties in the Sheridan district. The Green Campbell Mining Co. treated about 8,000 tons of gold ore in its 25-ton amalgamation-concentration mill and ranked second in output in the district. The mill and property were closed in late 1942, but the mill is expected to

reopen to treat chrome ore from local producers.

Tidal Wave district.—The output from the district in 1942 came from several small lode mines and was of two classes—gold and lead. The largest producers of gold ore were the Agitator and Carolina mines and the largest producers of lead ore the Last Chance and Keystone

mines.

Virginia City district.—In 1942 virtually all the ore produced in the Virginia City district was gold and gold-silver ore shipped crude to smelters. The principal producers were the Prospect, U. S. Grant, Kearsarge, Alameda, Easton, and Bartlett properties. R. E. Davis operated a dry-land dredge in 1942 on Barton Gulch, washed 83,945 cubic yards of gravel, and recovered virtually all the placer gold produced in the district.

Washington district.—The Gold Creek Mining Co. operated its bucket dredge in 1942 until November 1, when all activity was suspended indefinitely. Approximately 400,000 cubic yards of gravel were washed, which yielded 1,445 ounces of fine gold and 263 ounces of

silver. Lode production was crude gold and lead ore shipped direct to smelters.

#### MINERAL COUNTY

Iron Mountain district.—Zinc-lead ore from the Little Anaconda group was shipped to the Bauer mill (Utah); it comprised the only output from the Iron Mountain district in 1942.

## MISSOULA COUNTY

Nine Mile district.—Most of the placer output from the Nine Mile district in 1942 came from operation of a dry-land dredge by the Beaver Dredging Co. from March 3 to June 2, when all placer activity was suspended for the duration of the war. During the operating period 267,000 cubic yards of gravel were treated, yielding 1,696 ounces of gold and 30 ounces of silver.

#### PARK COUNTY

Emigrant Creek district.—The Emigrant Dredging Co. operated its 10-cubic foot electrically powered Yuba dredge from January 1 until October 15, 1942, when all work was suspended for the duration of the war. During its active period the dredge treated 1,048,668 cubic yards of gravel, which yielded 4,315 ounces of gold and 615 ounces of silver.

New World district.—The McLaren Gold Mines Co. operated its Estelle property and 100-ton flotation mill in 1942 until October 28, with a shut-down between May 21 and July 1. During the active periods in 1942 the mill treated 19,809 tons of gold ore, making 753 tons of copper concentrates (rich in gold), which were shipped to Washoe. All operations were suspended indefinitely after the mill was destroyed by fire on October 28. The Irma Mines, Inc., operated its Irma property until August 15, when Willow Creek Mines, Inc., Montana Operation, took over the property and worked it until December 19 to permit sampling the mine. In 1942 the Irma property produced an aggregate of about 2,500 tons of zinc-lead ore, which was milled in the Irma mill, and 67 tons of crude lead ore, which was shipped direct to East Helena.

shipped direct to East Helena.

Sheepeater (Jardine) district.—The Jardine Mining Co., only operator in the Jardine district in 1942, closed its mine and 225-ton amalgamation-concentration mill in January 1942. A program to develop the arsenic ore bodies in the mine was undertaken October 1, 1942, under

contract with the Chemical Warfare branch of the Army.

#### PHILLIPS COUNTY

Little Rockies district.—The Ruby Gulch Mining Co. worked the Ruby Gulch property in 1942 until the last of August, when operations were suspended indefinitely. During 8 months of activity about 45,600 tons of gold ore were treated in the company 300-ton cyanidation mill. The Little Ben Mining Co. suspended operations at the Little Ben mine in June.

## POWELL COUNTY

Finn district.—Ray W. Crumb operated a dry-land dredge in Madison Gulch and produced nearly all the placer output of the Finn district in 1942.

から とこれを とるなる はないない ないかい

Nigger Hill district.—Hopkins & Sons Mining Co. operated the Charter Oak mine throughout 1942 and was the chief producer in the district. The first 7 months of the year were spent in developing the property and building a 50-ton flotation mill. In August the mill was put into operation, and during the rest of the year 573 tons of silver ore were treated, which made 28 tons of lead concentrates. The remainder of the output was ore of several classes shipped crude to smelters and came chiefly from the Lilly group, Evening Star, and Cyclone properties.

Zozell (Emery) district.—The Bonanza mine, operated by the Bonanza Leasing Co. in 1942, was by far the chief source of mineral output in the Zozell district. It yielded 1,706 tons of gold ore shipped crude to a smelter. Other producers in the district were the Hidden Hand, Emma Darling, and Bull Moose properties, from which crude

ore was shipped to smelters.

#### RAVALLI COUNTY

Overwich district.—A dragline dredge was operated by the J. L. Shiely Co., Inc., on Hughes Creek in the Overwich district from April 6 to June 16, 1942.

#### SANDERS COUNTY

Eagle district.—The Jack Waite mine extends over the State line into Idaho; however, all production in 1942 came from that portion within Montana. The property was operated throughout 1942 by the American Smelting & Refining Co. and produced 22,752 tons of zinc-lead ore containing 19,111 ounces of silver, 3,758,630 pounds of lead, and 1,032,940 pounds of zinc. The ore was milled in the company 300-ton flotation plant and made 2,209 tons of lead concentrates and 819 tons of zinc concentrates. In addition, the mine produced 443 tons of high-grade crude lead ore, which was shipped direct to East Helena. The grade of mill ore treated was lower in 1942 than in 1941. The 300-ton flotation plant, situated in Idaho, was active one shift a day, 6 days a week in 1942.

Revais Creek district.—The Green Mountain Mining Co. operated the Drake property in 1942, treated about 800 tons of ore in its 50-ton

flotation mill, and made 32 tons of copper concentrates.

Other districts.—C. N. Franck produced 269 tons of gold ore from the Shoestring No. 1 mine in the Vermillion district in 1942; it was shipped to Washoe. Operators of the Glaucus mine in the Plains district shipped 10 tons of copper ore crude to Washoe.

## SILVER BOW COUNTY

Output of all metals except copper from mines in Silver Bow County decreased in 1942 owing to curtailment of operations at all zinc mines of the Anaconda Copper Mining Co. after May 25. The following table gives the output of mines in Silver Bow County, which includes the Butte or Summit Valley district, in 1941 and 1942 and the total from 1882 to the end of 1942.

Production of gold, silver, copper, lead, and zinc in Silver Bow County, Mont. 1941-42, and total, 1882-1942, in terms of recovered metals

	Mines pro- duc- ing	Ore (short tons)	Gold (lode and placer) (fine ounces)	Silver (lode and placer) (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)	Total value
1941 1942	1 65 38			8, 993, 693 8, 123, 788	254, 863, 000 280, 698, 000	17, 260, 900 14, 411, 000	76, 140, 400 58, 626, 000	\$44, 195, 725 46, 942, 464
1882-1942		(2)	1, 975, 192	525, 901, 025	8 6, 147, 029	3 222, 942	<sup>3</sup> 1, 539, 204	2, 465, 049, 603

<sup>1</sup> Corrected figure


Butte or Summit Valley district.—All productive mines of the Anaconda Copper Mining Co. maintained capacity operations during 1942 commensurate with the current supply of available labor. company-operated zinc mines at Butte were operated until in May. when the labor shortage at both zinc and copper mines became so acute that all zinc mines were closed and the mine labor was transferred to the copper mines. During the remainder of the year only a small production came from company-owned zinc mines, and it was incidental to the mining of copper. The aggregate output from all copper mines, dumps, and tailings piles exceeded that in 1941 by 10 percent. The copper concentrator at Anaconda treated 3,287,817 tons of copper ore from company-owned Butte mines compared with 2,869,051 tons in 1941, and 4,589 tons of mine-water precipitates were treated compared with 4,500 in 1941. In addition the copper concentrator at Anaconda treated 241,526 tons of mine dump material averaging about 1 percent copper compared with 405,862 tons in 1941, 727,464 tons of Old Works tailings and Upper Old Works tailings averaging slightly over 1½ percent copper, and 16,365 tons of New Works tailings averaging less than 1 percent; crude ore smelted amounted to 18,193 tons, and old tailings totaled 42,268 tons. North Butte Mining Co. property was reopened in 1942 and operated by the Anaconda Copper Mining Co. under a contract agreement. The output from this property amounted to 46,781 tons of copper milling ore and 55 tons of copper precipitates. During the period of activity at the zinc mines they produced 307,900 tons of zinc-lead ore compared with 472,133 tons in 1941. All ores were treated in the company zinc concentrator at Anaconda. Development work in 1942 at all copper mines comprised 232,748 feet of drifts, 201 feet of shafts, and 19,301 feet of diamond drilling; at all zinc mines, 33,068 feet of drifts, 991 feet of shafts, and 1,607 feet of diamond drilling. tions were continued throughout 1942 at the Emma mine, leased from the Butte Copper & Zinc Co. by the Anaconda Copper Mining Co. Production amounted to 13,583 tons of zinc-lead ore and 30,286 tons of zinc-lead sulfide concentrates (middlings from the treatment of manganese ore), all treated at the zinc concentrator. Development at the Emma mine comprised 1,263 feet of shafts and 1,882 feet of diamond drilling in the zinc section of the mine and 26,454 feet of drifts and 1,725 feet of diamond drilling in the manganese section. At other manganese mines operated by the Anaconda Copper Mining Co. at Butte, development totaled 3,864 feet of drifts and 479 feet of diamond drilling. It is notable that the total advance of 297,397

Figures not available. Short tons.

feet (excluding shafts) in 1942 was higher than in any year of record. Lessees of the Anaconda Copper Mining Co. operated several company properties; the most productive were the Poulin, which yielded zinc-lead ore containing over 4,000,000 pounds of zinc and nearly a million pounds of lead, and the Black Rock group, which yielded 2,218 tons of silver ore and 46 tons of zinc ore. All lessee operations were on a much smaller scale in 1942 than in 1941.

Highland district.—The Butte Highland Mining Co. operated the Highland group (Tilton) and its 75-ton cyanide mill in 1942 until about April, when the property was closed owing to the low grade of

the ore.



# GOLD, SILVER, COPPER, LEAD, AND ZINC IN NEVADA

#### (MINE REPORT)

By CHARLES WHITE MERRILL AND H. M. GAYLORD

#### SUMMARY OUTLINE

	Page		Page
Summary	415	Mining industry—Continued.	_
Calculation of value of metal production		Ore classification	420
Mine production by counties	419	Metallurgic industry	420
Mining industry	419	Review by counties and districts	426

## SUMMARY

The total value of gold, silver, copper, lead, and zinc recovered from ore, old tailings, and gravels in Nevada decreased 8 percent in 1942 compared with 1941; all five metals except copper decreased in both quantity and value. Copper production—167,326,000 pounds—was the largest in the State's history; in value it exceeded each year since Higher wages, enlistment of miners in the armed forces, migration of miners to war industries and military construction jobs, rising prices of supplies and equipment and difficulties in obtaining them, increased taxes, and fixed prices for gold and silver were factors in reducing the total output, despite Nevada's great mineral resources and War Production Board Order the war demand on many of them. L-208 of October 8, 1942, terminated activities at some large gold mines (many small and some large had closed previously). Probably base-metal mines obtained some much-needed skilled miners as a There was very little eviresult of the order and thereby benefited. dence, however, that the order itself had much effect on the 1942 decline in gold production (because of reprieves) or in stimulating basemetal output.

Comparing 1942 with 1941, gold output decreased 19 percent and silver 36 percent in both quantity and value; copper increased 6 percent in quantity and 9 percent in value; and lead decreased 44 percent in quantity and 34 percent in value and zinc 33 percent in quantity and 16 percent in value. Of the total value of the five metals copper comprised 57 percent, gold 29 percent, silver 7 percent, zinc 5 percent,

and lead 2 percent.

White Pine County increased its lead over other counties and produced 59 percent of the State total value of the five metals; this county stood first in output of copper and gold. Lincoln County produced 8 percent of the State total value and ranked second to White Pine County; it led in the State in silver, zinc, and lead output.

All tonnage figures are short tons and "dry weight"; that is, they do

not include moisture.

Yardage figures used in measuring material treated in placer operations are "bank measure"; that is, the material is measured in the ground before treatment.

The value of metal production herein reported has been calculated

at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zine 4
1938	Per fine ounce \$35,00	Per fine ounce \$ \$0.646+	Per pound \$0.098	Per pound \$0.046	Per pound \$0.048
1939 1940	35. 00 35. 00	6.678十 7.711十	. 104 . 113	.047	.052
1941 1942	35. 00 35. 00	7.711+ 7.711+	.118 .121	.057 .067	. 075 . 093

¹ Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.
² ¹ Treasury buying price for newly mined silver.
³ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.
⁴ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.
⁵ \$0.64646464.

Mine production of gold, silver, copper, lead, and zinc in Nevada, 1938-42, and total, 1859-1942, in terms of recovered metals

Year		Mines producing 1 Ore, old tailings, etc. (short		and placer)	nd placer) Silver (lode and		
	Lode	Placer	tons)	Fine ounces	Value	Fine ounces	Value
1938	795 891 895 799 434	130 104 115 78 49	5, 880, 021 6, 894, 999 8, 338, 259 8, 799, 635 9, 383, 379	296, 434 361, 518 383, 933 366, 403 295, 112	\$10, 375, 190 12, 653, 130 13, 437, 655 12, 824, 105 10, 328, 920	4, 355, 471 4, 316, 029 5, 175, 928 5, 830, 238 3, 723, 435	\$2, 815, 658 2, 929, 668 3, 680, 660 4, 145, 947 2, 647, 776
1859-1942 2			(3)	25, 070, 558	556, 031, 206	584, 429, 765	536, 926, 177

Year	Cor	per	Le	ad	Zi		
	Pounds	Value	Pounds	Value	Pounds	Value	Total value
1938 1939 1940 1941	92, 338, 000 133, 194, 000 156, 908, 000 157, 822, 000 167, 326, 000	\$9, 049, 124 13, 852, 176 17, 730, 604 18, 622, 996 20, 246, 446	9, 358, 000 8, 472, 000 14, 998, 000 19, 246, 000 10, 752, 000	\$430, 468 398, 184 749, 900 1, 097, 022 720, 384	17, 888, 000 12, 456, 000 23, 666, 000 30, 258, 000 20, 394, 000	\$858, 624 647, 712 1, 490, 958 2, 269, 350 1, 896, 642	\$23, 529, 064 30, 480, 870 37, 089, 777 38, 959, 420 35, 840, 168
1859-1942 2	4 1, 549, 157	440, 740, 968	4 522, 335	55, 828, 767	4 269, 036	37, 359, 926	1, 626, 887, 044

<sup>1</sup> Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to

Gold.—Gold production in Nevada continued near the 1941 rate through May 1942, but thereafter a decline set in; the September output was about two-thirds that of May. The production curve showed no downward break for October and November but declined

property.

<sup>2</sup> Compiled by Chas. W. Henderson, supervising engineer, field offices, Denver, Colo. From 1904 (when first satisfactory annual canvass of mine production was made) to 1942, inclusive, the output was as follows: Gold, 13,243,681.51 ounces, valued at \$311,547,973; silver, 296,016,916 ounces, \$199,767,954; copper, 1,547,231 tons, \$440,094,340; lead, 284,544 tons, \$33,192,205; zinc, 269,036 tons, \$37,359,926; total value, \$1,021,962,398.

<sup>2</sup> Figures not available.

<sup>4</sup> Short tons.

somewhat in December, indicating some reaction to War Production Board Order L-208, but general economic conditions overshadowed the Government order in causing the decrease from 1941 in output of gold. The 10 leading gold-producing mines in 1942 supplied 74 percent of Nevada's output, and the 5 leaders contributed 56 percent. By the end of the year, however, operations at all but the leading three had been suspended. The War Production Board permitted Getchell Mine, Inc., to continue because of its byproducts—tungsten and arsenic—and gave limited permission to operate to the Manhattan dredge, because the operators were in a narrow canyon and equipment was subject to destruction by cloudbursts.




FIGURE 1.—Value of mine production of gold, silver, copper, lead, and zinc and total value in Nevada, 1860-1942.

Ten leading gold-producing mines in Nevada in 1942, in order of output

			North Ca	ii		
Rank	Mine	District	County	Rank 1941	Operator	Source of gold
1 2 3	Getchell Ruth and Copper Flat Pit. Coppermines group	Potosi Robinson	Humboldt White Pine.	1 2 3	Getchell Mine, Inc Nevada Consolidated Copper Corporation. Consolidated Copper-	Gold ore. Copper ore.
4	Manhattan dredge	Manhattan Silver City	NyeLvon	4 9	mines Corporation.  Manhattan Gold Dredging Co.  Dayton Dredging Co	Dredge.
6 7	Goldacres Overman	Bullion Comstock	Lander Storey	42 8	Willow Creek Mines, Inc. Consolidated Chollar Gould & Savage Min- ing Co.	Dragline dredge. Gold ore. Do.
8	Keystone	do	do	10	Dayton Consolidated Mines Co. and lessees.	Do.
9	Northumberland	Northumber- land.	Nye	7	Northumberland Mining	Do.
10	Gold Standard	Imlay	Pershing	6	Standard Cyaniding Co	Do.

Silver.—The 10 leading silver-producing mines in Nevada in 1942, listed in the following table, produced 61 percent of the State total recoverable silver; the first 2 yielded almost one-fourth of the total. As in preceding years, most of the silver was a byproduct of ore

mined chiefly for other metals; only 25 percent was derived from straight silver ore.

Ten leading silver-producing mines in Nevada in 1942, in order of output

Rank	Mine	District	County	Rank in 1941	Operator	Source of silver
1 2 3 4	Nivloc Mizpah Bristol Silver Pioche Nos. 1 and 2	Silver Peak Tonopah Jack Rabbit Pioche	Esmeralda Nye Lincoln do	1 4 5 2	Desert Silver, Inc Various lessees Bristol Silver Mines Co. Combined Metals Re- duction Co.	Silver ore. Gold-silver ore. Copper ore. Zinc-lead ore.
5	Rip Van Winkle	Merrimac	Elko	18	Rip Van Winkle Con- solidated Mining Co.	Lead ore.
6 7	Financier Dan Tucker	Pioche Sand Springs	Lincoln Churchill	24 6	W. A. Free Summit King Mines, Ltd.	Do. Gold-silver ore and old tail- ings.
8	Ruth and Copper Flat Pit.	Robinson	White Pine.	11	Nevada Consolidated Copper Corporation.	Copper ore.
9 10	Adelaide Crown El Dorado-Rover group.	Gold Run Eldorado Can- yon.	HumboldtClark	16 7	Adelaide Crown Mines_ El Dorado-Rover Min- ing Co.	Gold-silver ore. Gold-silver ore and old tail- ings.

Copper.—Over 98 percent of the recoverable copper output of Nevada in 1942 came from mines operated by the following companies: The Nevada Consolidated Copper Corporation, working the Ruth mine at Ruth and the open pit at Copper Flat (both in the Robinson district, White Pine County); the Consolidated Coppermines Corporation, working the Coppermines group at Kimberly (also in the Robinson district); and the Mountain City Copper Co., working the Mountain City mine at Mountain City (in the Cope district, Elko County). The State copper-production capacity was increased in March when the International Smelting & Refining Co. placed in operation its new 350-ton concentrator at the Copper Canyon Lease property (in the Battle Mountain district, Lander County).

property (in the Battle Mountain district, Lander County).

Lead.—Over half the lead produced in Nevada in 1942 was mined in the Pioche district, Lincoln County, where Pioche Nos. 1 and 2 operated by the Combined Metals Reduction Co., the Financier operated by the Salt Lake-Pioche Mining Co. and lessees, and the Prince operated by the Prince Consolidated Mining Co. were the leading properties. Other important producers were the Rip Van Winkle Consolidated Mining Co., Rip Van Winkle mine (in the Merrimac district, Elko County); Hall Bros. Co., Inc., Tybo mine (in the Tybo district, Nye County); and Bristol Silver Mines Co., Bristol Silver mine (in the Jack Rabbit district, Lincoln County).

Zinc.—As in recent years, zinc production was centered in the Pioche district, Lincoln County, where 88 percent of the State total was mined in 1942. The Combined Metals Reduction Co. and the Prince Consolidated Mining Co. were the principal producers. The addition of a slag-fuming plant for recovering zinc from lead blast-furnace slag and from oxidized zinc ore at the Tooele (Utah) plant of the International Smelting & Refining Co. offered a new market to some Nevada miners.

#### MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in Nevada in 1942, by counties, in terms of recovered metals

	Mine	es pro-			C	lold				r (lode and
County				ode	P	lacer	T	otal	1	olacer)
	Lode	Placer	Fine ounces	Value	Fine ounces	Value	Fine ounces	Value	Fine	
Churchill Clark Douglas Elko Esmeralda Eureka Humboldt Lander Lincoln Lyon Mineral Nye Pershing Storey Washoe White Pine	27 - 1 - 38 - 41 - 23 - 26 - 23 - 29 - 22 - 22 - 24 - 24	3 4 5 2 3 3 2 2 2 11 13 1	833 53, 360 19, 877 2, 693 3, 021 848 18, 094 10, 711 33, 150	\$142, 030 281, 225 35 51, 695 443, 170 29, 155 1, 867, 600 696, 695 105, 735 29, 680 332, 290 374, 885 1, 160, 250 10, 500 2, 752, 330	76 59 206 45 108 21,660 21 24,645 478 12	2, 065 7, 210 1, 575 3, 780 758, 100 758, 100 862, 575 16, 730 420	12, 721 1, 039 53, 405 19, 985 2, 693 24, 681 42, 739 11, 189 33, 162 300	\$142, 030 281, 225 54, 355 54, 355 36, 365 1, 869, 175 699, 475 863, 835 30, 415 1, 495, 865 391, 615 1, 160, 670 2, 753, 870	200, 0 201, 5 1, 0 210, 9 714, 6 17, 9 252, 2 124, 0 739, 2 26, 6 50, 2 448, 9 22, 2 298, 6 408, 0	562 143, 33; 621 149, 98; 680 508, 21; 603 12, 73; 649 179, 377; 617 525, 70; 619 35, 70; 619 35, 70; 619 35, 70; 619 35, 70; 619 35, 70; 619 319, 22; 621 212, 377; 622 4, 92;
Total, 1941	434 799		247, 758 329, 506	8, 671, 530 11, 532, 710	47, 354 36, 897	1, 657, 390 1, 291, 395	295, 112 366, 403	10, 328, 920 12, 824, 105	3, 723, 4 5, 830, 2	35 2, 647, 776 38 4, 145, 947
County		Coppe	er	Lead				Zine		(Da4a) les
County	Poun	đs	Value	Pound	is	Value	Pound	ls Va	lue	Total value
Churchill Clark Douglas Elko Esmeralda	14, 352, 2,		1, 736, 592 242 243	22,0	000	\$2,010 11,390 124,620 1,474 2,010	456, 0 896, 0		2, 408 3, 328	\$286, 275 478, 356 793 2, 148, 883 955, 168 51, 348
Eureka Humboldt Lander Lincoln Lyon Mineral	16, 1, 272, 1, 380, 108, 18,	000 000 000 000	1, 936 153, 912 166, 986 13, 068 2, 178	222, 196, 6,640, 3 316,6	000 000 000	14, 874 13, 132 444, 880 21, 172	8, 0 2, 0 18, 004, 0	000 1,67	744 186 4, 372 3, 578	2, 066, 106 954, 895 2, 906, 193 895, 875 103, 047
NyePershingStoreyWashoeWhite Pine	18,	000 000 000 000 1	726 2, 178 726 8, 167, 666	64,0	000	71, 824 4, 288 134 8, 576	16, 0 866, 0		1, 488 0, 538	1, 887, 638 415, 394 1, 373, 046 16, 352 21, 300, 802
Total, 1941	167, 326, 157, 822,		0, 246, 446 8, 622, 996	10, 752, 6 19, 246,		720, 384 , 097, 022	20, 394, 0 30, 258, 0	000 1,89 000 2,26	6, 642 9, 350	35, 840, 168 38, 959, 420

<sup>&</sup>lt;sup>1</sup> Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to property.

## MINING INDUSTRY

Expansion of production at the three large copper mines in Nevada has been the principal cause of the increasing tonnage of ore treated since 1940. Production of copper ore increased 15 percent in 1942 compared with 1941, and the quantity of dry and siliceous ore and old tailings sold or treated declined 26 percent. There was a short-lived revival of old-tailings cyanidation in Nevada, when a 1,000-ton plant went into operation at Millers, Esmeralda County, March 6.

The connected-bucket dredge of the Manhattan Gold Dredging Co. in the Manhattan district, Nye County, was again the largest producer

of placer gold and the fourth largest of total gold in the State; the dragline operation in the Silver City district, Lyon County (started January 1, 1941, by the Dayton Dredging Co.), made the second-largest placer-gold and the fifth-largest total gold output in the State in 1942. In addition to these large placer operators, 1 dragline dredge, 2 nonfloating washing plants with mechanical excavators, 2 hydraulic mines, 36 (19 dry) small-scale hand-method mines, and 7 drift mines were in operation. Quicksilver consumption at placer mines was 162 pounds in 1942.

#### ORE CLASSIFICATION

The following table classifying ores produced in Nevada in 1942 shows that 84 percent of the tonnage (including old tailings) sold or treated was copper ore, 9 percent gold ore and old tailings, 4 percent gold-silver ore and old tailings, 1 percent each zinc-lead ore and silver ore, and the remainder zinc ore, lead ore, and lead-copper ore.

Details of ore classification are given in the chapter of this volume

on Gold and Silver.

Ore and old tailings sold or treated in Nevada in 1942, with content in terms of recovered metals

성화를 수하게 된다. 아르고 제 기업이 소개한 학생에 발하는 사이와 모르고	Materia l treat							
Source	Ore	Old tailings	Gold	Silver	Copper	Lead	Zinc	
Dry and siliceous gold ore	Short tons 895, 992 259, 148 80, 837	1,777 78,826	Fine ounces 136, 793 26, 509 3, 000	1, 238, 568	25, 600	371, 400		
Copper ore	1, 235, 977 7, 904, 443 25, 673 7 47, 522 81, 916	6, 408	78, 548	558, 330 434, 355 44 87, 425	1167, 169, 500 70, 700 600 5, 400	714, 200 5, 229, 200 2, 200 778, 900	89, 80	
Total, lode mines	9, 295, 538	87, 841	247, 758 47, 354		1167, 326, 000	10, 752, 000	20, 394, 00	
Total, 1941	9, 295, 538 8, 789, 982				1167, 326, 000 157, 822, 000	10, 752, 000 19, 246, 000	20, 394, 00 30, 258, 00	

<sup>&</sup>lt;sup>1</sup> Includes 6,172,600 pounds from precipitates.

#### METALLURGIC INDUSTRY

Of the 9,383,379 tons of lode material from Nevada sold or treated during 1942, 85 percent went to concentrating mills, 13 percent to amalgamation and cyanidation mills, and 2 percent to smelters; of the total, less than 1 percent was old tailings—all amalgamated, cyanided, or smelted. Flotation was employed at concentration mills to the virtual exclusion of gravity concentration. Of the gold recovered as bullion, cyanidation supplied 94 percent and amalgamation 6 percent; of the silver recovered as bullion, 99.5 percent was derived by cyanidation and 0.5 percent by amalgamation. The total quantity of crude ore and old tailings shipped to smelters in 1942 declined 29 percent compared with 1941.

A STATE OF THE PARTY OF THE PAR

The new 350-ton flotation mill built by the International Smelting & Refining Co. at the Copper Canyon mine in the Battle Mountain district, Lander County, began operation in March 1942. The year 1942, however, witnessed suspension of operations at many mills, particularly after promulgation of Order L-208 by the War Production Board.

Quicksilver consumed in Nevada in 1942 at mills using amalgamation totaled 930 pounds in recovering 8,521 ounces of gold and 7,239

ounces of silver from 89,857 tons of material.

Data obtained on cyanide consumption in 1942 at Nevada mills are nearly complete. In the treatment of 796,193 tons of ore, 36,968 tons of old tailings, and 200 tons of concentrates, 389,867 pounds of 91-percent sodium cyanide and 1,490,526 pounds of commercial-grade calcium cyanide (50-percent NaCN equivalent) were used, with a recovery of 104,984 ounces of gold and 1,213,552 ounces of silver; in terms of 98-percent NaCN the consumption was 1,092,401 pounds, or 1.31 pounds to the ton of material treated compared with 0.98 pound in 1941.

Mine production of metals in Nevada in 1942, by methods of recovery, in terms of recovered metals

Method of recovery	Material treated	Gold	Silver	Copper	Lead	Zine
Ore and old tailings amalgamated	Short tons 89,857	Fine ounces 8, 521	Fine ounces 7, 239	Pounds	Pounds	Pounds
Ore, old tailings, sands, slimes, and concentrates cyanided	1, 167, 244	134, 064	1, 506, 409			
Flotation Gravity	327, 966 94	83, 107 854	947, 561 8, 497	153, 652, 300	6, 000, 000 19, 300	18, 757, 100
Ore and old tailings smelted Precipitates	143, 032	21, 212	1, 233, 749	7, 501, 100 6, 172, 600	4, 732, 700	1, 636, 900
Total, lode mines Total, placers		247, 758 47, 354	3, 703, 455 19, 980	167, 326, 000	10, 752, 000	20, 394, 000
Total, 1941		295, 112 366, 403	3, 723, 435 5, 830, 238	167, 326, 000 157, 822, 000	10, 752, 000 19, 246, 000	20, 394, 000 30, 258, 000

All of Nevada's custom cyanide mills suspended operations during 1942. The leading ones were operated by the Dayton Consolidated Mines Co., Silver City, Lyon County; Adelaide Crown Mines, Gold Run district, Humboldt County; Silver State Milling Corporation, Westgate, Churchill County; and Ohio Mines Corporation, Gold Point, Esmeralda County. Most of these mills received the major part of their mill feed from mines controlled by the mill operators. The 500-ton selective-flotation mill, operated by the Combined Metals Reduction Co. at Pioche, Lincoln County, treated zinc-lead and zinc ores upon a custom basis for several neighboring mines and also milled company zinc-lead ore. The Nevada Consolidated Copper Corporation treated all the copper ore produced by the Consolidated Coppermines Corporation upon a contract basis, in addition to milling its own ore. The Nevada Consolidated Copper Corporation also operated the McGill copper smelter, which was Nevada's only smelter and the most important metallurgical plant in the State.

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in Nevada in 1942, by types of mills and by counties, in terms of recovered metals

#### AMALGAMATION MILLS

	Material treated R			Recovered in bullion		Concentrates smelted and recovered metal						
County	: Ore <sup>1</sup>	Old tail- ings	Gold	Silver	Con- cen- trates pro- duced	Gold	Silver	Copper	Lead	Zinc		
Olhill	Short tons 41	Short tons	Fine ounces 13	Fine ounces 10	Short tons	Fine ounces	Fine ounces	Pounds	Pounds	Pounde		
Churchill Clark Elko	21, 160 670		370 219	564 181	271	2, 504	28, 770					
Esmeralda Humboldt	43 1,812		55 551	14 272								
Lander Lincoln	1,412 70		497 11	83 32								
Lyon Mineral	33 101	50	14 26	6 18								
Nye Pershing Storey	6, 974 2, 879 52, 827	1, 499	2, 650 1, 721 2, 133	2, 802 1, 378 1, 788	24 1	346 32	626 26		200			
Washoe White Pine	282		251 10	89	i	4	4					
Total, 1941	88, 308 250, 335	- 1, 549 367	8, 521 25, 757	7, 239 19, 120	297 390	2, 886 3, 832	29, 426 44, 754	1,000	200			

## CYANIDATION MILLS

Churchill	15, 103	3, 339	4, 032	198, 217	1	9	95			
Clark	60, 928	18, 530	4, 250	158, 923	33	281	7, 103		900	
Douglas		4	1	1,066						
Elko	266		140	2,042						
Esmeralda	81, 725	56,600	8,844	666, 856						
Humboldt	385, 505	120	50, 680	141, 036	59	324	1, 562	1,600	9,800	3, 900
Lander	85, 207		12,662	2, 921						
Lyon	7,025	53	2, 922	15,842	5	66	11	100		
Mineral	321		184	1,894						
Nye	80, 658		10, 860	11, 488						
Pershing	119, 543		8, 498	6, 982						
Storey	249, 894	1,589	30, 985	296, 802						
Washoe	34		. 5	382						
White Pine		800	1	1,958						
	1, 086, 209	81, 035	134, 064	1, 506, 409	98	680	8,771	1, 700	10, 700	3, 900
Total, 1941	1, 420, 579	5, 161	185, 170	2, 236, 009	42	601	10, 189	1, 100	10, 700	3, 900
10181, 1941	1, 420, 579	0, 101	100, 170	2, 200, 009	44	001	10, 109			
Grand total:										
1942	1, 174, 517	82, 584	142, 585	1, 513, 648	395	3, 566	38, 197	1,700	10,900	3, 900
	1, 670, 914	5, 528	210, 927	2, 255, 129	432	4, 433	54, 943	1,000	10, 500	0, 500
1041	1,010,914	0,020	410, 941	4, 400, 140	404	7, 400	02, 940	1,000		

<sup>&</sup>lt;sup>1</sup> Figures under "Ore" include both raw ore and concentrates amalgamated or cyanided, but not raw ore concentrated before amalgamation or cyanidation of concentrates.

# Mine production of metals from concentrating mills in Nevada in 1942, in terms of recovered metals

# BY COUNTIES

			Concentrates smelted and recovered metal									
a de la lagrada forma espe Megasia esperada esperada A regular forma esperada esp	Ore treated	Concen- trates produced	Gold	Silver	Copper	Lead	Zinc					
Elko	Short tons 121,398 2	Short tons 26, 473	Fine ounces 467	Fine ounces 185, 088 34	Pounds 9, 664, 000	Pounds 1, 480, 300	Pounds 830, 800					
Humboldt Lander Lincoln Mineral Nye	8, 500 86, 640 130, 393 200 5, 724	1, 768 6, 458 23, 658 9 271	1, 208 4, 729 1, 463	106, 575 56, 566 293, 014 5, 057 39, 909	13,000 1,145,800 1,000 2,300	204, 000 300 4, 210, 400 7, 000	17, 914, 200					
Pershing White Pine	7, 654, 570	269, 015	72, 526	231, 295	142, 824, 500	87, 200 2, 200 17, 000	8, 200					
Total, 1941	8, 007, 455 7, 042, 097	327, 665 325, 648	80, 395 73, 209	917, 861 1, 565, 093	153, 650, 600 147, 168, 200	6, 008, 400 14, 463, 600	18, 753, 200 29, 270, 000					
	ву с	LASSES	OF CON	CENTRA	TES							
Dry gold Dry gold-silver		165 1	60 1	386 34		4,700	5, 500					
Copper Lead Zine		299, 793 9, 085 18, 621	77, 513 2, 306 515	302, 484 516, 209 98, 748	153, 609, 900 34, 000 6, 700	300 5, 708, 600 294, 800	509, 900 18, 237, 800					
		327, 665	80, 395	917, 861	153, 650, 600	6, 008, 400	18, 753, 200					

# Gross metal content of concentrates produced from ores mined in Nevada in 1942, by classes of concentrates

Class of concentrates	Concen- trates	Gross metal content								
Class of concentrates	produced	Gold	Silver	Copper	Lead	Zine				
Dry gold	Short tons 517 34 299, 793 9, 091 18, 625	Fine ounces 3, 335 282 77, 513 2, 316 515	Fine ounces 30, 900 7, 137 302, 484 516, 745 98, 792	Pounds 2, 329 155, 894, 621 42, 597 8, 352	Pounds 10, 905 963 349 5, 953, 290 330, 448	Pounds 8,719 809,294 20,294,393				
Total, 1941	328, 060 326, 080	83, 961 77, 642	956, 058	155, 947, 899 150, 737, 250	6, 295, 955 15, 193, 908	21, 112, 406 34, 258, 607				

Mine production of metals from Nevada concentrates shipped to smelters in 1942, in terms of recovered metals

## BY COUNTIES

	Concen- trates	Gold	Silver	Copper	Lead	Zine
Churchill	Short tons	Fine ounces	Fine ounces	Pounds	Pounds	Pounds
Clark	304	2, 785	35, 873		900	
Elko	26, 473	467	185, 088	9, 664, 000	1, 480, 300	830, 800
Esmeralda		i	34	0,002,000	2, 200, 000	000,000
Humboldt	1,827	1, 532	108, 137	14,600	213, 800	3,900
Lander	6, 458	4,729	56, 566	1, 145, 800	300	
Lincoln	23, 658	1, 463	293, 014	1,000	4, 210, 400	17, 914, 200
Lyon	5	66	11	100		
Mineral	9		5, 057		7,000	
Nye	271	1	39, 909	2,300	87, 200	
Pershing	36	346	949		2,400	8, 200
Storey	1	32	26			
Washoe	200 01	TO 700	001 005	140 004 700		
White Pine	269, 015	72, 526	231, 295	142, 824, 500	17, 000	
	328, 060	83, 961	956, 058	153, 652, 300	6, 019, 300	18, 757, 100
Total, 1941	326, 080	77, 642	1, 620, 036		14, 463, 600	29, 270, 000
	BY CLASS	ES OF CO	NCENTRA	TES		
Dry gold	517 34	3, 335 282	30, 900 7, 137	1, 700	9, 200 900	5, 500
				I have a consequent	900	
Dry gold-silver			200 404	152 600 000		
Dry gold-silver Copper Lead	299, 793 9, 091	77, 513 2, 316	302, 484 516, 745	153, 609, 900 34, 000	300 5, 713, 900	509, 90

Gross metal content of Nevada crude ore and old tailings shipped to smelters in 1942, by classes of material

328,060

18, 757, 100

	Material	shipped	Gross metal content						
Class of material	Ore	Old tailings	Gold	Silver	Copper	Lead	Zinc		
Dry and siliceous gold	Short tons 18, 551 31, 367 16, 826 57, 401 9, 214 7 2, 375 535	Short tons  322 26  6, 408	Fine ounces 11, 303 6, 886 564 1, 035 1, 403	Fine ounces 30, 742 474, 878 209, 073 255, 846 261, 762 44 693 711	Pounds 44, 821 14, 870 9, 225 113, 894, 767 67, 996 733 6, 667 405	Pounds 5, 166 201, 498 270, 037 796, 768 3, 764, 858 2, 312 70, 715 122, 844	Pounds 28, 319 5, 292 3, 018 142, 307 217, 592 1, 479, 398 255, 191		
Total, 1941	136, 276 197, 544	6, 756 4, 125	21, 212 40, 937	1, 233, 749 1, 941, 040	1 14, 039, 484 11, 096, 748	5, 234, 198 5, 267, 456	2, 131, 117 1, 209, 269		

<sup>&</sup>lt;sup>1</sup> Includes 6,236,762 pounds of copper contained in precipitates.

Mine production of metals from Nevada crude ore and old tailings shipped to smelters in 1942, in terms of recovered metals

## BY COUNTIES

	Materia	l shipped					
	Ore	Old tailings	Gold	Silver	Copper	Lead	Zinc
	Short tons	Short tons	Fine ounces	Fine ounces	Pounds	Pounds	Pounds
hurchill lark			630	1,696 6,202		30,000 169,100	456,000
ilko	13, 299		651	23, 600	4, 688, 000	379, 700	65, 200
Smeralda	4,654		3, 762	47, 748	2,000	22,000	
Sureka Iumboldt	2, 121		833	17, 889	2,000	30,000	4, 100
Iumboldt	2,697 7,846	4	597 1,989	2, 794 64, 433	1,400 126,200	8, 200 195, 700	2,000
anderincoln	24, 223	200	1, 219	446, 228	1, 379, 000	2, 429, 600	89, 80
yon	617	200	19	165	107, 900		
/Ineral	4,918		638	43, 223	18,000	309,000	146,00
Туе	15, 767	6, 430	4,583	385, 711	3,700	984, 800	7, 800
ershing			146 40	12,751 6,545	18,000 6,000	61,600 2,000	1,000
Vashoe Vhite Pine		122	6, 101	174.764	1 7, 321, 500	111,000	866, 000
V III 06 I III 0	· · · · · · · · · · · · · · · · · · ·						2 2 2 2 3
	136, 276	6, 756	21, 212	1, 233, 749	113, 673, 700	4, 732, 700	1, 636, 90
Cotal, 1941	197, 544	4, 125	40, 937	1,941,040	10, 652, 800	4, 782, 400	988, 00
	BY CLA	SSES O	г мат	ERIAL			
Ory and siliceous gold	18, 551		11,303	30, 742	41,700	3, 200	
Ory and siliceous gold-silver	31, 367	322	6,886	474, 878	12,600	161, 100	4, 10
Dry silver	16, 826	26	564	209, 073	8, 100	171, 100	2,00 89,80
Copper	57, 401		1,035	255, 846	1 13, 559, 600 45, 400	713, 900 3, 530, 900	158,00
_ead	9, 214	6, 408	1, 403	261, 762 44	45, 400	2, 200	100,00
Lead-copperine	2,375		14	693	5, 400	52, 500	1, 185, 30
inc-lead	535		7	711	300	97, 800	197, 70
	136, 276	6, 756	21, 212	1, 233, 749	1 13, 673, 700	4, 732, 700	1, 636, 90

<sup>1</sup> Includes 6,172,600 pounds of copper from precipitates.

# REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, lead, and zinc in Nevada in 1942, by counties and districts, in terms of recovered metals 1

County and district 1		es pro-	Ore and old		Gold			Copper	Lead	Zinc	Total value
	Lode	Placer	tailings	Lode	Placer	Total	placer) 8				Value
Churchill County:			Short tons	Fine ounces	Fine ounces	Fine ounces	Fine ounces	Pounds	Pounds	Pounds	
Alpine	1		15	7		7	3				\$2
Broken Hills	) 1		1	5		5	4				1
Desert	1		25	1		. 1	3				
Eastgate			896	270		270	2, 513				11, 2
Fairview	2		1,304	163		163	17,062		30,000		19, 8
Holy Cross	1		14				350				2
Wonder	2	1	1,818	202		202	17, 993				19,8
Clark County:		1									
Eldorado Canyon	6		99, 826	7, 121		7, 121	198,090		1,000		390, 1
Searchlight	10		1,017	897		897	2, 205		200		32, 9
Yellow Pine	11		1,266	17		17	1, 267		168,800	456,000	55, 2
Douglas County: Silver Glance	1		4	1		1	1,066				7
Elko County:	. 1	1									1
Centennial			367	150		150	363		1,600		5, 6
Contact			629	11		. 11	966	58, 200			8, 1
Cope	3	2	116, 757	347	_42	389	18, 883	14, 148, 600			1,739,0
Delano	2		547	2		2	8, 435	2, 400	114, 700	1,800	14, 2
Ferber	1		6				. 11	500			1000
Gold Circle	4		377	248		248	2, 132				10, 1
Island Mountain		. /1			34	34	3				1, 1
Jarbidge			1,063	350		350	2, 569	100			14, (
Lime Mountain	1		686	173		173	824	21, 500			9, 2
Mardis	[ 1		43	150		150	100	600	200	:::-::-	5,
Merrimac	1		12, 416	28		. 28	168, 694	24, 300	1, 455, 600	829, 800	298,
Mud Springs	1		1				4		600		
Railroad	2		1,371	10		. 10	4,843	15,000	217,800	1,900	20, 3
Rock Creek	1		5	2		. 2	703				_
Spruce Mountain			198	2		. 2	2,004	2, 400	53, 500	2,000	5, 8
Tecoma			53	1		. 1	236		15,400		1, 2
Warm Creek	2		313				20		300	60, 500	5, €
Esmeralda County:	1 -					1					
Desert	1		57	144		144	94				5, 1
Divide	5		858	439		439	6, 580				20,0
Dyer.	1		46				2,496	100	1,800		1, 9
Goldfield	7		2,736	1,736			944	1,000	200		61, 5
Hornsilver	) 9		3,067	1,633		1,633	36, 511	200	4,300		83, 4
Klondyke Lida		3	78	16	57	. 16 58	742	200	8,000		1, 6 2, 0

Lone Mountain	: 1		35	1		1	278	500	5, 900		689 105
Silver Peak	12		79, 544	8, 459		8, 459	649, 206		1,800		757, 844 70
Sylvania Tonopah 4	ī	1	56, 600	230	2	230	17, 767				20, 684
Eureka County:	2		1,077	451	İl	451	6, 598	2,000	15, 400		21, 751
Eureka	15		1,044	382	206	382 206	11, 291 14		14,600		22, 377 7, 220
Lynn Humboldt County:	1	3			200						
Awakening Barrett Springs	5 5		1, 594 8, 782	297 1, 472		297 1, 472	198 106, 678	13,000	204, 100		10, 536 142, 628
Battle Mountain	2 5	2	26 92, 437	11 4.831	45	4, 876	136, 837	400	11, 700	8,000	388 269, 542
Paradise Valley	3		50	86		86	21				3,025
PotosiLander County:	1		295, 624	46, 625		46, 625	8, 442	2,600	6, 200		1, 638, 608
Battle Mountain	12 6	2	92, 857 86, 235	6, 126 12, 987	106 2	6, 232 12, 989	105, 962 15, 013	1, 196, 500 75, 100	188, 700 1, 200		450, 891 474, 458
Bullion Hilltop	ĭ		25	190		190	516				7,017
McCoy New Pass	1 2		500 1, 412	69 497		69 497	200 83				2, 557 17, 454
Reese River	4		80	8		8	2, 243	400	6, 100	2,000	2, 518
Comet	1		50	7 101		7 101	191 578		100		388 3, 946
Eagle ValleyFerguson	1 1		98 202	317		317	1,028				11,826
GroomJack Rabbit	1 2		4, 085 17, 394	2 141		2 141	5, 549 242, 644	1,800 1,372,900	382, 600 713, 300	89, 800	29, 868 399, 745
Pahranagat	i		139	78		78	1,017 1,014	400 300	15, 400 300		1, 803 3, 507
Pennsylvania Pioche	11		101 132, 817	2,047		2,047	487, 253	4,600	5, 528, 300	17, 914, 200	2, 455, 110
Lyon County: Buckskin	١,	1 .	187	63		63	58	1,400			2, 415
Cambridge	. 1		62 242	132		2 132	1.198	-,			71 5, 472
PalmyraSilver City		2	5, 942	2, 365	21,660	24, 025	19, 973				855, 078
TalapoosaYerington	. 3		768 576	378 11		378 11	5, 268 170	106, 500			16, 976 13, 393
Mineral County:	1			12		12	52				457
AuroraBell	. 2		1,765	102		102	9, 381	16,000	194, 600	146,000	38, 793
ColumbusEast Walker			957 3	294 2		2	12, 139 7	2,000	92, 700		25, 375 75
Garfield	. 2		2, 379 317	343 60			22, 974 5, 251		13, 800 11, 900		29, 267 6, 631
Hawthorne	. 3		18	12		12	339		3,000		862
RandRegent		2	19 73	11 12		11 33	14 52				395 1, 192
Megunt	٠, ٠			'	• 3	•	·	,			

See footnotes at end of table.

Mine production of gold, silver, copper, lead, and zinc in Nevada in 1942, by counties and districts, in terms of recovered metals—Continued

County and district	Mine duc	s pro- ing	Ore and old	Gold			Silver (lode and	Copper	Lead	Zine	Total value
County and district	Lode	Placer	tailings	Lode	Placer	Total	placer)				Value
e County:			Short tons		Fine ounces	Fine ounces	Fine ounces	Pounds	Pounds	Pounds	
Athens	1		138	53		53	35-				\$1,
Bellehelen	1		7	3		3	73				
Belmont	1		22				245				
Bruner	1		14	17		17	44				
Bullfrog	6		831	398		398	1,762	400			15
Currant Creek	1		17	15		15	11				
Eden	1		2	3		3	54				
Golden Arrow	1		53	49		49	201				Ţ
Hannapah	2		21	179		179	495				
Jackson			75	70		70	384				
Johnnie	1	1	90	3	15	18	3 ].			,	
Mammoth			37	16		16	367		400		004
Manhattan		8	3,024	1,808	24, 589	26, 397	9, 873				930
Morey	1		287	17		17	6, 868		2, 700		
Northumberland	1		79, 445	10, 145		10, 145	8, 577				36
Phonolite	1		71	37		37	411				
Quartz Mountain	1		149	18		18	2,043	600	35, 400		70.00
Reveille	1		2				21		300		_
Round Mountain	2	2	3, 911	931	41	972	2, 492				3
San Antone		1	528	17		17	6, 179				
Silver Bow	3		550	33		33	7, 851				1
Tonopah 4			11, 555	3, 480		3, 480	316, 945	500			34
Trov			1	5		5	8 .				
Tybo			8, 991	786		786	43, 689	2, 200	945, 900		12
Union		1	5, 729	2		2	40, 251	2, 300	87, 300		3
shing County:			, , ,								
Antelope	4	(6)	233	70	31	101	921	12, 800	2, 200	8, 200	
Central			195	8		8	6, 822	300	17, 400		
Imlay		3	118, 733	8, 306	36	8, 342	5, 697				29
Jersey		l	96	5	l	5	2, 395	700	33, 400	7, 800	- 1 1
Kennedy		1	161	63		63	1, 925	4, 200	700		
Rochester		4	258	93	34	127	464		200		
Rosebud		(6)	750	130	27	157	963				(
Sawtooth		2	l		14	14					
Seven Troughs	7	l	2, 449	1.852	l	1,852	1,797				66
Sierra			61	65		65	35				
Staggs	i i		40	68		68	976		7, 300		
Trinity			6	1		ī	86		2,800		
Unionville		2		1 1 2 3 3 3	10	10		************			
Washiki			60	50		50	3 .				
Willow Creek		2	1	1	326	326	170				1

Storey County: Comstock	24	1.	281, 616	33, 150	12	33, 162	298, 654				1, 373, 046
Washoe County:	1		39	1		1	83	1,000	200		228 212
JumboPeavine.	1 1		24 183 261	6 44 249		44 249	6, 830 104	5, 000	1,800		7, 123 8, 789
White Horse White Pine County:	7		337	249		210	214	1, 700	19, 000	97, 700	10. 717
Aurum Bald Mountain Cherry Creek	1 5		290 3, 569	43 313		43 313	596 36, 436	10, 900			3, 248 36, 865
Eagle	1		12 46	1 2		1 2	177 273	5, 400	4, 900		489 917
Granite Newark	1 1		51 4	87		87	24 138				3, 062 98 120, 262
OsceolaPiermont	2 1	3	3, 412	3, 367	44	3, 411 6 74, 609	1, 233 1, 339 273, 939	7 150, 126, 400	80. 100	768, 300	1, 162 21, 048, 229
Robinson	23 5		7, 692, 785 9, 084	74, 609 208		208	90, 544 641	1,000	4, 800		71, 667
Ward	3		3, 307 15, 571	3, 530		3, 530	2, 472 162, 322	600 78, 500	19, 200 300		3, 152 248, 497
Other districts 8	434	49	9, 383, 379	247, 758	47, 354	295, 112	3, 723, 435	7 167, 326, 000	10, 752, 000	20, 394, 000	35, 840, 168
TOTAL INCANDET TOTAL	101	10	2, 230, 0.0		1				<u> </u>	<u> </u>	

Only those districts shown separately for which Bureau of Mines is at liberty to publish figures; other producing districts listed in footnote 8 and their output included under "Other districts."
 Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to property.
 Source of total silver as follows: 3,703,455 ounces from lode mines and 19,980 ounces from placers.
 Tonopah district lies in both Esmeralda and Nye Counties.
 Battle Mountain district lies in both Humboldt and Lander Counties.
 Output from property not classed as a "mine."
 Includes 6,172,600 pounds of copper from precipitates.
 Includes 6,172,600 pounds of copper from precipitates.
 Includes following districts: Dixie Valley and Sand Springs in Churchill County; Dolly Varden in Elko County; National and Varyville in Humboldt County; Pine Grove in Lyon County; and Millett in Nye County.

#### CHURCHILL COUNTY

The Silver State Milling Corporation, reorganized successor to the Westgate Mining & Milling Corporation, discontinued its custom-cyanide-mill operations at Westgate early in 1942. Thus, the operators of a number of local properties in Churchill County were left without a profitable market for their ores.

Fairriew district.—Lessees shipped lead ore to a smelter from the Chalk Mountain mine during 1942. Several groups of lessees worked the Nevada Hills mine; 1,253 tons of gold-silver ore shipped to custom cyanide mills yielded 159 ounces of gold and 15,366 ounces of silver.

Wonder district:—Erwin & Wauchope operated the Nevada Wonder mine from January 1 to June 30, 1942; 1,671 tons of gold-silver ore shipped to a custom-cyanide mill yielded 199 ounces of gold and 14,993 ounces of silver.

## CLARK COUNTY

Eldorado Canyon district.—The El Dorado-Rover Mining Co. operated the Quaker City, Magnolia, Crown, and Nevada Eagle claims from January 1 to December 8, 1942; 25,587 tons of gold-silver ore and 530 tons of old tailings were treated in the company 150-ton cyanide mill; cyanide precipitates contained 2,641 ounces of gold and 123,482 ounces of silver, and 33 tons of concentrates shipped to a smelter contained 281 ounces of gold, 7,103 ounces of silver, and 963 pounds of lead. The Diamond Gold Mining Co. operated the Techatticup and Jubilee mines from January 1 to December 1; ore was treated in a 200-ton cyanide mill. W. W. Hartman operated the Wall Street mine throughout the year; gold ore was treated in a 60-ton amalgamation-flotation mill, and the resulting concentrates were shipped to a smelter.

Yellow Pine (Goodsprings) district.—J. Jacobson shipped oxidized zinc ore from the Green Monster mine to a smelter during 1942. The Defense Metals Co. shipped lead and zinc-lead ores from the Hoosier Hammons & Reed and the Ingomar Mining Co., Inc., operated the Ingomar group; 176 tons of zinc-lead ore containing 27,637 pounds of lead and 106,738 pounds of zinc were shipped to a smelter. Defense Metals Co. and R. K. Hamilton worked the Root Zinc mine during 1942; shipments consisted of 89 tons of lead ore containing 770 ounces of silver and 50,308 pounds of lead; 102 tons of zinc ore containing 10,248 pounds of lead and 82,170 pounds of zinc; and 29 tons of zinc-lead ore containing 8,193 pounds of lead and 7,501 pounds L. F. Jacobson shipped 169 tons of zinc-lead ore containing 28,606 pounds of lead and 85,754 pounds of zinc from the Sultan mine between May 20 and October 1, when the smelting company ceased buying the ore and the operation was discontinued. H. C. Kennedy operated the Whale mine from March 19 to December 31; 44 tons of zinc ore shipped to a smelter contained 1,580 pounds of lead and 30,099 pounds of zinc. The principal product of the mine, however, was vanadium. The Yellow Pine Lease shipped zinc ore from the Yellow Pine mine to a smelter.

## ELKO COUNTY

Contact district.—The Marshall Mining Co. operated the Delano and Allen mines as a unit from April 1 to December 31, 1942; 605

TO A CONTRACT OF THE PARTY OF T

tons of copper ore containing 10 ounces of gold, 895 ounces of silver,

and 56,997 pounds of copper were shipped to a smelter.

Cope (Mountain City) district.—The Mountain City Copper Co. (third-largest copper producer in Nevada) was active throughout 1942; part of the ore was treated in the company 400-ton flotation mill, and high-grade copper ore was shipped for direct smelting.

Delano district.—Lessees on the Cleveland mine shipped 192 tons of lead ore containing 1 ounce of gold, 4,655 ounces of silver, 1,592 pounds of copper, 58,823 pounds of lead, and 1,198 pounds of zinc

during 1942. Lead ore was produced at the Net mine.

Dolly Varden district.—The International Smelting & Refining Co. carried on development at the Victoria mine from July to December, 1942; copper ore produced during this work and by a lessee was shipped to a smelter.

Gold Circle district.—Percy Collins operated the Miners Gold mine from July 1 to November 1, 1942; 205 tons of gold-silver ore were shipped to a custom cyanide mill, where 101 ounces of gold and 1,890

ounces of silver were recovered.

Jarbidge district.—A. M. Ross recovered 97 ounces of gold and 75 ounces of silver from the treatment of 350 tons of ore mined at the

O. K. mine in 1942.

Lime Mountain district.—Lime Mountain Consolidated operated the Lime Mountain mine from May 4 to September 30, 1942; 686 tons of ore shipped to a smelter contained 173 ounces of gold, 824 ounces of

silver, 22,186 pounds of copper, and 28,319 pounds of zinc.

Merrimac (Lone Mountain) district.—The Rip Van Winkle Consolidated Mining Co. treated 12,416 tons of lead ore in the company flotation mill and shipped to a smelter 1,137 tons of lead concentrates (containing 23 ounces of gold, 162,322 ounces of silver, 20,745 pounds of copper, and 1,505,103 pounds of lead) and 938 tons of zinc concentrates (containing 5 ounces of gold, 6,372 ounces of silver, 8,352 pounds of copper, 17,874 pounds of lead, and 932,347 pounds of zinc).

Spruce Mountain (Black Forest) district.—Lessees operated the Black Forest mine from January 1 to July 1, 1942; 141 tons of lead ore containing 1 ounce of gold, 1,710 ounces of silver, and 41,176 pounds of lead were shipped to a smelter. E. Parker worked the Humbug mine from January 1 to July 1 and shipped to a smelter 44 tons of lead ore containing 1 ounce of gold, 201 ounces of silver, 509 pounds of copper, and 13,160 pounds of lead.

Warm Creek (Polar Star) district.—Turner & Stoddard shipped to a smelter 312 tons of oxidized zinc ore (containing 6 ounces of silver and 85,034 pounds of zinc) from the dumps of the Polar Star mine between

May 2 and June 22, 1942.

## ESMERALDA COUNTY

Divide district.—Various lessees on the Divide mine shipped 812 tons of ore containing 430 ounces of gold and 5,929 ounces of silver during 1942.

Dyer district.—J. A. Molini & Son operated the Green Monster mine from March 1 to October 31, 1942; 46 tons of silver ore shipped to a smelter contained 2,496 ounces of silver and 2,996 pounds of lead.

Goldfield district.—Gold ore produced by various sets of lessees on the Goldfield Consolidated Mines Co. property was shipped to a smelter during 1942; 2,269 tons of gold ore contained 1,192 ounces of gold, 503 ounces of silver, and 1,414 pounds of copper.

Hornsilver (Gold Point) district.—The Ohio Mines Corporation suspended operations of the Ohio group mine and the custom cyanide

mill at the property during 1942.

Silver Peak district.—Price & Kunde worked the Francis mine and shipped ore to a smelter. E. L. Cord, operating as the Prescott Lease, worked the Mary mine from January to April 1942, when the lease was quit-claimed; 24,943 tons of ore treated in the company 350-ton flotation-cyanidation-leaching plant yielded bullion containing 5,213 ounces of gold and 1,674 ounces of silver, and 354 tons of ore shipped to a smelter contained 482 ounces of gold, 285 ounces of silver, and 1,109 pounds of copper; a small part of the production was the result of lease operation. Desert Silver, Inc., worked the Nivloc mine, leading silver producer in the State since 1938; the ore was treated in the company 175-ton cyanide mill.

Tonopah district.—In 1942 the Bradshaw Syndicate, Inc., completed construction of a 1,000-ton cyanide plant, designed to treat tailings at Millers. Operations began March 6 and were continued by the company until June, when Willow Creek Mines, Inc., took over the management. In all, 56,600 tons of old tailings yielding 230 ounces of gold and 17,767 ounces of silver were treated; work was stopped

before the end of the year.

## EUREKA COUNTY

Cortez district.—Lessees operated the Roberts group in 1942; 694 tons of gold-silver ore shipped to a smelter contained 158 ounces of gold, 5,993 ounces of silver, 1,135 pounds of copper, and 24,763 pounds of lead. Lessees operating the Ventura and Maid Queen mines shipped to a smelter 383 tons of ore containing 293 ounces of gold and 605 ounces of silver.

Eureka district.—Eureka Corporation, Ltd., operated the Oswego mine intermittently between January and October 1942; 342 tons of ore shipped to a smelter yielded 157 ounces of gold and 155 ounces of silver. Silver Rock Mines, Inc., worked the Wynona mine from January 1 to October 2 and shipped to a smelter 220 tons of silver

ore containing 5 ounces of gold and 7,829 ounces of silver.

Lynn district.—C. E. and I. H. Lee operated the Gold Coin No. 1 mine on Sheep Creek from March 10 to July 27, 1942; 1,200 cubic yards of gravel treated by ground sluicing yielded 116 ounces of gold and 7 ounces of silver.

## HUMBOLDT COUNTY

Awakening (Slumbering Hills) district.—Lessees operated the Alabama mine during 1942; 339 tons of ore treated by amalgamation yielded 58 ounces of gold and 15 ounces of silver, and 59 tons of ore shipped to a custom cyanide mill yielded 19 ounces of gold and 33 ounces of silver. Austin Bros. Gold Mining Co. worked the Jumbo mine from May 17 to November 11; 1,135 tons of ore treated in the company 25-ton amalgamation mill yielded 206 ounces of gold and 144 ounces of silver.

• Barrett Springs (Ten-mile) district.—West Coast Mines, Inc., operated the Pansy Lee mine during the early months of 1942; gold-

THE SEAL OF SEAL SEAL WAY DE

大学、大一大学のでは、100 mm 大学に、100 mm 大

silver ore was treated in the company 150-ton flotation mill, and the resulting lead concentrates were shipped to a smelter. The King Gold mine was active.

Gold Run (Adelaide) district.—Adelaide Crown Mines operated the Adelaide Crown mine from January 1 to December 7, 1942; in addition to treating ore from this mine, the company treated 1,556 tons

of custom ore from 12 shippers.

Potosi district.—Getchell Mine, Inc., operated the Getchell mine throughout 1942. Oxidized ores (treated by cyanidation without roasting) were exhausted in September, and thereafter all ore was given a roast before cyanidation; additions were made to the roasting plant for the recovery of arsenic. In addition, a 250-ton scheelite flotation plant was installed, operation of which began in September.

## LANDER COUNTY

Battle Mountain district.—Symanzik & Wrobel worked the Armour mine from March 1 to December 16, 1942; 2,864 tons of silver ore shipped to a smelter contained 185 ounces of gold, 30,262 ounces of silver, and 217,323 pounds of lead. The International Smelting & Refining Co. started operation of its newly constructed 350-ton flotation mill at the Copper Canyon mine early in 1942 and shipped copper ore and copper concentrates to a smelter. Broyles & Wilson worked the Independence mine the entire year and shipped to a smelter 555 tons of gold-silver ore containing 404 ounces of gold and 10,889 ounces of silver. Franzini & Macdonald worked the Palisades-Pinnacle group of claims from June 1 to November 15 and shipped to a smelter 226 tons of gold-silver ore containing 26 ounces of gold, 2,588 ounces of silver, and 8,895 pounds of lead.

Bullion district.—Willow Creek Mines, Inc., acting as manager for

the Consolidated Goldacres Co., operated the Goldacres mine from March 7 to December 31, 1942, except for a short shut-down caused by War Production Board Order L-208; ore was treated by cyanidation. S. Dunham operated the Gold Quartz mine. The Little Gem Operating Co. shipped copper ore and flotation copper concentrates from the Little Gem mine.

New Pass district.—New Pass Mines worked the New Pass mine from January 1 to July 1, 1942; ore was treated in a 25-ton amalgam-W. H. Smith worked the Thomas W. mine from January 1 to December 15; 315 tons of ore treated in a 5-stamp mill yielded 146 ounces of gold and 23 ounces of silver.

## LINCOLN COUNTY

Groom district.—The I. M. C. Corporation and D. Sheahan operated the Groom mine during 1942; a 50-ton concentration-flotation mill was constructed, and lead ore and lead concentrates were shipped to a smelter.

Jack Rabbit (Bristol) district.—The Bristol Silver Mines Co. operated the Bristol Silver mine throughout 1942 and shipped ore to a

smelter.

Pennsylvania district.—Crowe, Phelps & Johnston worked the Pennsylvania mine from January 1 to June 20, 1942; 46 tons of ore shipped to a smelter contained 54 ounces of gold and 564 ounces of silver.

Pioche district.—Amalgamated Pioche Mining & Smelting Corporation and a lessee shipped to a smelter silver ore, lead ore, and goldsilver old tailings from the Amalgamated Pioche mine. Lake-Pioche Mining Co. Apex and Financier mines were worked by lessees, who shipped lead ore to smelters; C. E. Bleak operated the Apex and W. A. Free the Financier. Ely Valley Mine worked the Ely Valley mine throughout 1942 and shipped zinc ore to the Combined Metals Reduction Co. custom mill at Pioche. Lessees worked the Nevada Volcano mine and shipped lead ore to a smelter. The Combined Metals Reduction Co. worked the Pioche Nos. 1 and 2 mines and treated the zinc-lead ore in the company mill at Pioche, except for a small quantity that was shipped to the company mill at Bauer, The Prince Consolidated Mining Co. shipped zinc ore to the Pioche custom mill of the Combined Metals Reduction Co. throughout the year and a small quantity of lead ore to a smelter. Bros. Co., Inc., shipped gold-silver ore from the Raymond Ely mine to a smelter during January and February; 1,406 tons of ore yielded 57 ounces of gold and 6,366 ounces of silver. Pioche Mines Consolidated, Inc., operated the Wide Awake mine through lessees from January 1 to September 30; lead ore was shipped to a smelter.

## LYON COUNTY

Silver City district.—The Dayton Consolidated Mines Co. operated the Dayton mine from January 1 to October 15, 1942, and treated, in the company cyanide plant, 5,050 tons of ore which yielded 1,526 ounces of gold and 8,067 ounces of silver. Ore from nearby mines operated by this company and 5,973 tons of ore received from 94 shippers upon a custom basis were treated at the mill. T. S. Franklin shipped ore from the Haywood mine to a custom cyanide mill. The Gold Rock Mining Co. shipped ore from the Silver King mine to a custom cyanide mill.

Yerington district.—Lessees worked the Mason Valley mine throughout 1942 and shipped to a smelter 551 tons of copper ore containing 3 ounces of gold, 113 ounces of silver, and 109,072 pounds of copper.

## MINERAL COUNTY

Bell (Simon) district.—Lesses worked the Olympic mine from January 1 to July 1, 1942, and shipped 88 tons of ore to a custom cyanide mill; 83 ounces of gold and 68 ounces of silver were recovered. Costa & Evansen worked the Simon Lead mine and shipped to a smelter 1,677 tons of lead ore containing 19 ounces of gold, 9,313 ounces of silver, 24,110 pounds of copper, 217,926 pounds of lead, and 199,924 pounds of zinc.

Garfield district.—The Mabel mine was operated by lessees in 1942; 23 tons of gold-silver ore shipped to a custom cyanide mill yielded 4 ounces of gold and 105 ounces of silver, and 1,434 tons of gold-silver ore shipped to a smelter contained 130 ounces of gold and 5,124 ounces

of silver.

## NYE COUNTY

Manhattan district—E. J. Hyde operated the Big Four mine in 1942; 100 tons of ore treated by amalgamation yielded 128 ounces of gold and 58 ounces of silver. J. L. Sullivan worked the Pathfinder

CAN THE PROPERTY OF THE PROPER

mine from January 1 to October 31 and panned 500 pounds of ore yielding 58 ounces of gold and 23 ounces of silver. J. Farrell and R. Graham shipped several lots of ore for treatment by amalgamation, cyanidation, and smelting; 128 tons of ore amalgamated yielded 134 ounces of gold and 56 ounces of silver, 12 tons of gold ore cyanided yielded 10 ounces of gold and 3 ounces of silver, and 8 tons of gold ore smelted yielded 12 ounces of gold and 25 ounces of silver. Manhattan Gold Dredging Co. (largest producer of placer gold in the State since 1939) operated throughout 1942; its electric connectedbucket dredge was equipped with 108 9%-cubic foot buckets. company was granted limited permission to operate after the issuance of War Production Board Order L-208 because the dredge was situated in a narrow canyon and subject to danger of cloudburst floods.

Morey district.—V. J. Barndt worked the Morey mine from January 1 to June 30, 1942, and shipped ore to smelters; 279 tons of silver ore yielded 15 ounces of gold and 5,441 ounces of silver, and 8 tons of lead ore contained 2 ounces of gold, 1,427 ounces of silver, and 2,839 pounds

of lead.

Northumberland district.—The Northumberland Mining Co. operated the Northumberland mine from January 1 to October 15, 1942; 79,445 tons of ore treated in the company 300-ton cyanide mill yielded

10,145 ounces of gold and 8,577 ounces of silver.

Tonopah district.—The Tonopah Belmont Syndicate operated the Tonopah Belmont mine from January 1 to October 7, 1942; 177 tons of gold-silver ore containing 55 ounces of gold and 5,209 ounces of silver were shipped to a smelter. A shipment of 16 tons of gold-silver ore from the Tonopah Extension mine to a smelter contained 54 ounces of gold and 5,506 ounces of silver; the long-idle 500-ton cyanide plant at the property was totally destroyed by fire October 23. eral sets of lessees worked parts of the Tonopah Mining Co. of Nevada property throughout 1942 and shipped gold-silver ore to a smelter. Gold-silver ore containing 572 ounces of gold and 50,388 ounces of silver was shipped to a smelter from the West End mine.

Tybo district.—Hall Bros. Co., Inc., and J. C. Jepson worked the Tybo mine during 1942 and shipped ore and old tailings to a smelter; 104 tons of gold-silver ore contained 7 ounces of gold, 823 ounces of silver, and 8,539 pounds of lead; 210 tons of silver ore contained 9 ounces of gold and 1,619 ounces of silver; and 6,408 tons of lead old tailings contained 612 ounces of gold, 22,389 ounces of silver, and

1.042.524 pounds of lead.

## PERSHING COUNTY

Imlay district.—The Standard Cyaniding Co. worked the Gold Standard and Lally mines in 1942 until operations were suspended

as a result of War Production Board Order L-208.

Jersey district.—I. D. Kelly worked the Rex mine from June 1 until the end of 1942; 96 tons of lead ore containing 5 ounces of gold, 2,395 ounces of silver, 789 pounds of copper, 34,313 pounds of lead, and 10,892 pounds of zinc were shipped to a smelter.

Staggs district.—The Twin Buttes Mining Syndicate constructed a 15-ton gravity-concentration mill between January 1 and May 10,1942, after which production was carried on until the end of the year.

## STOREY COUNTY

Comstock district.—Lessees shipped 152 tons of gold ore from the Chollar mine to a custom cyanide mill in 1942; 113 ounces of gold and 1,435 ounces of silver were recovered. A large quantity of company gold ore was treated in the 100-ton flotation mill at the Consolidated Virginia mine between January 1 and October 24; the concentrates were shipped to a custom cyanide mill. Sutro Tunnel Coalition, Inc., worked the Crown Point and Yellow Jacket mines the entire year. The Dayton Consolidated Mines Co. and lessees shipped gold ore from the Justice mine to the company custom cyanide mill at Silver City; the same company operated the Keystone and New York mines from January 1 to October 8 and treated ore in its cyanide mill. The Consolidated Chollar Gould & Savage Mining Co. operated its open pit at the Overman mine from January 1 to December 7; 141,505 tons of ore treated by cyanidation yielded 11,752 ounces of gold and 94,017 ounces of silver.

WHITE PINE COUNTY

Aurum district.—The Grand Deposit Mining Co. worked the Grand Deposit mine from June 15 to December 31, 1942; 280 tons of oxidized zinc ore containing 137,614 pounds of zinc were shipped to a zinc slag-fuming plant. The company received a \$10,000 development loan from the Reconstruction Finance Corporation in November.

Bald Mountain district.—E. R. Wagner shipped 290 tons of gold ore, containing 43 ounces of gold, 596 ounces of silver, and 11,148 pounds of copper, from the Pioneer mine to a smelter in 1942.

Granite district.—Lessees worked the Stinson mine during 1942; 4 tons of ore treated by amalgamation yielded 10 ounces of gold and 2 ounces of silver, and 47 tons of ore shipped to a smelter contained 77 ounces of gold and 22 ounces of silver.


Osceola district.—The Gilded Age Mining Co. worked the Gilded Age mine from January 1 to October 15, 1942; 3,388 tons of ore containing 3,359 ounces of gold and 1,220 ounces of silver were shipped to a small or

Robinson district.—The Nevada Consolidated Copper Corporation, which had been the operating subsidiary of the Kennecott Copper Corporation in Nevada for many years, merged with the parent corporation and became known as the Kennecott Copper Corporation, This corporation, which Nevada Mines Division, at the end of 1942. operated the Ruth mine at Ruth, the open pit at Copper Flat, the McGill flotation concentrator (daily capacity, 20,000 tons) and the McGill copper smelter, both at McGill, was the largest industrial organization in Nevada. As well as being the State's leading copper producer, the company stood second in gold and eighth in silver output. The Consolidated Coppermines Corporation, second-largest copper producer and third-largest gold producer in the State in 1942, was active throughout the year; copper ore mined on company account was shipped to the McGill concentrator, and small quantities of highgrade copper ore and zinc-lead ore were shipped for direct smelting. C. Caviglia shipped gold ore from the Chainman mine to a smelter. S. M. Robison shipped zinc-lead ore and zinc ore from the Columbia mine to smelters during the year. Lessees on the Cuba mine shipped 4,440 tons of gold-silver ore containing 362 ounces of gold and 18,669 ounces of silver to a smelter during 1942. Benson Bros. shipped 30

tons of lead ore, containing 1 ounce of gold, 334 ounces of silver, and 21,667 pounds of lead, from the Goldenrod mine to a smelter. Gold ore from the Hayes mine was shipped to a smelter. A lessee worked the Jupiter mine from January 1 to November 16 and shipped gold ore to a smelter. Lessees worked the Phoenix mine from July 1 to December 31; 536 tons of ore shipped to a smelter contained 134 ounces of gold and 1,048 ounces of silver. The Ely Gold Mining Co. shipped gold-silver ore and zinc ore from the Revenue mine to a smelter. The Willard Leasing Co. worked the Willard mine from May to the end of the year; 675 tons of oxidized ore containing 694,913 pounds of zinc were shipped for treatment.

Taylor district.—Lessees worked the Gore mine; 5,711 tons of silver ore containing 113 ounces of gold and 62,709 ounces of silver were shipped to a smelter. Lessees worked the Mineral Farm No. 1 mine and shipped to a smelter 394 tons of silver ore containing 9 ounces of

gold and 4,742 ounces of silver.



# GOLD, SILVER, COPPER, LEAD, AND ZINC IN NEW MEXICO

(MINE REPORT)

## By Chas. W. HENDERSON

## SUMMARY OUTLINE

$\mathbf{Page}$		Page
Summary 439	Mining industry	444
Calculation of value of metal production 440		444
Mine production by counties	Metallurgic industry	445
	Review by counties and districts	448
	· 통령· 하는데 마음이 되는데 그를 보고 있다. 나는데 가장 사람들이 되는데 하는데 하는데 보다 보고 있다. 그 사람들이 다른데	

## SUMMARY

Production of both copper and zinc in New Mexico in 1942 was larger in quantity than in any previous year; that of lead was slightly




FIGURE 1.—Value of mine production of copper and zinc and total value of gold, silver, copper, lead, and zinc in New Mexico, 1870–1942. The value of gold, silver, and lead produced annually has been relatively small.

less than in 1941 but greater than in 1940. The output of gold decreased 57 percent and that of silver 49 percent, in both quantity and value. The total value of the recovered output of the five metals was \$29,542,885 in 1942, compared with \$25,471,416 in 1941. Copper represented 66 percent and zinc 29 percent of the total value in 1942.

Production of gold, silver, copper, lead, and, more particularly, zinc in 1942 was affected by several factors, all precipitated by the war. In an effort to stimulate the production of copper, lead, and zinc the Government, through its agency, the Metals Reserve Co., announced that effective February 1, 1942, premium prices of 5 cents per pound for copper and 2% cents per pound for both lead and zinc would be paid for these metals produced in excess of fixed The ceiling prices for these metals on that date (and they have so remained through June 1943) were: Copper, electrolytic, 11.775 cents per pound f. o. b. Atlantic seaboard refineries; lead, 6.50 cents (New York); zinc, 8.25 cents (St. Louis). The quota for each mining company or mine was based upon the 1941 output. Some of the mines in New Mexico that received basic quotas on their 1941 production have since received, by negotiation with the Metals Reserve Co., a reduction in the quota tonnage. On December 1,

THE PARTY OF THE P

1942, arrangements for additional premium payments for overquota metal output were announced by the Metals Reserve Co. Operators who could argue their inability to maintain present rate of production without loss of money or who could assure additional output were eligible for these additional Government subsidies for copper in several steps of 5 cents a pound for each step, or for lead

and zinc in steps of 2\% cents a pound. War Production Board Gold Mining Limitation Order L-208, issued October 8, 1942, has been widely assigned in the Western States as the outstanding single cause for the marked decrease in production of gold in 1942. An analysis of gold lode and placer operations in New Mexico in 1942 disclaims this conception for New Mexico. All gold lode operations that would have been affected by this order ceased operations during the first 6 months of 1942. Of the three producing dredging operations in New Mexico in 1942, two were forced to cease operating by the order; the other stopped production in April 1942. Factors forcing the closure of these gold properties were many, and their effect was not confined to 1942. Many operators began to feel the acute scarcity of skilled labor in Higher wages in war-material factories and at army cantonments, rising operating costs, difficulty of obtaining replacement equipment, and the drain on company personnel imposed by the selective service were all responsible for the early closing of the gold properties.

These factors confronted gold-mine operators as early as January 1941, and the complexity of government priorities regulations also had their effect upon zinc, lead, and copper operations in New Mexico in 1942. Operators were confronted with increasing demands for metals and decreasing supply of labor. Marked absenteeism at the larger operations in 1942 forced the companies to carry 30 percent more employees on the rolls to insure a near complement of men for each shift. At the end of 1942 the mine operators in New Mexico found themselves facing the problem of meeting increasing demand with insufficient labor in 1943.

All tonnage figures are short tons and "dry weight"; that is, they do not include moisture.

The value of metal production herein reported has been calculated at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold <sup>1</sup>	Silver 2	Copper 3	Lead 4	Zine 4
1938 1939 1940 1941 1942	Per fine ounce \$35.00 35.00 35.00 35.00 35.00	Per fine ounce 5 \$0.646+ 6.678+ 7.711+ 7.711+ 7.711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057 .067	Per pound \$0.048 .052 .063 .075

The following table shows the number of mines in New Mexico producing gold, silver, copper, lead, and zinc and their annual output of ore and metals from 1938 to 1942; also the total production from 1848 to 1942. The report of this series for 1929 (chapter of Mineral Resources of the United States, 1929, pt. 1, pp. 729–759) gives the yearly production of each important metal-producing district in New Mexico from 1904 to 1929, inclusive. Subsequent records year by year may be found in annual issues of Mineral Resources and Minerals Yearbook.

Mine production of gold, silver, copper, lead, and zinc in New Mexico, 1938-42, and total, 1848-1942, in terms of recovered metals

Year			produc- ng	Ore (short	Gold (lode	and placer)	Silver (	lode and cer)
rear		Lode	Placer	tons)	Fine ounces	Value	Fine ounces	Value
1938 1939 1940 1941 1942		166 214 164 145 78	164 168 179 103 48	2, 414, 857 4, 977, 375 7, 089, 903 7, 530, 226 8, 221, 512	43, 050 36, 979 35, 943 27, 845 11, 961	\$1, 506, 750 1, 294, 265 1, 258, 005 974, 575 418, 635	1, 229, 860 1, 400, 878 1, 407, 839 1, 328, 317 676, 170	\$795, 061 950, 899 1, 001, 130 944, 581 480, 832
1848-1942				(1)	2, 160, 741	48, 960, 128	65, 952, 746	51, 631, 038
Year		Copper		Le	ad	Zi	ne	Total
1 ear	Poun	ds	Value	Pounds	Value	Pounds	Value	value
1938 1939 1940 1941 1942	40, 878, 92, 284, 139, 696, 146, 956, 160, 200,	000   9, 000   15, 000   17,	006, 044 597, 536 785, 648 340, 808 384, 200	9, 898, 000 10, 784, 000 7, 644, 000 9, 336, 000 9, 216, 000	\$455, 308 506, 848 382, 200 532, 152 617, 472	56, 472, 000 58, 712, 000 60, 626, 000 75, 724, 000 92, 922, 000	\$2,710,656 3,053,024 3,819,438 5,679,300 8,641,746	\$9, 473, 819 15, 402, 572 22, 246, 421 25, 471, 416 29, 542, 885
1848-1942	2 1, 097,	544 328,	263, 183	2 249, 292	24, 149, 203	<sup>2</sup> 658, 291	83, 528, 270	536, 531, 822

<sup>&</sup>lt;sup>1</sup> Figures not available.

Gold and silver produced at placer mines in New Mexico, 1938-42, in terms of recovered metals

	Ge	old	Sil	ver	(Data)		G	lold	Silv	ver	
Year	Fine ounces	Value	Fine ounces	Value	Total value	Year	Fine ounces	Value	Fine ounces	Value	Total value
1938 1939 1940	2, 626 3, 474 2, 928	121, 590		142		1941 1942	2, 488 1, 247	\$87, 080 43, 645			\$87, 282 43, 741

Gold.—Mine production of gold in New Mexico decreased from 27,845 fine ounces in 1941 to 11,961 ounces in 1942. The principal gold-producing districts in 1942 were: Central, Grant County, which contributed 34 percent of the State output of recovered gold; Mogollon, Catron County, 28 percent; Steeple Rock, Grant County, 12 percent; Lordsburg, Hidalgo County, 11 percent; Las Animas, Sierra County, 5 percent; and Pinos Altos, Grant County, 3 percent. Dry and siliceous ores yielded 45 percent of the State total gold; copper ore, 40 percent; lead, zinc, zinc-lead, and lead-copper ores, over 4 percent; and placers, over 10 percent.

<sup>2</sup> Short tons.

Silver.—Mine production of silver in New Mexico was 676,170 fine ounces in 1942 compared with 1,328,317 ounces in 1941. The Central district contributed 33 percent of the State total in 1942, Mogollon 31 percent, Lordsburg 13 percent, Steeple Rock 9 percent, San Simon 7 percent, Magdalena 4 percent, and Swartz 1 percent. Dry and siliceous ores yielded 47 percent of the total silver; zinc and zinc-lead ore 29 percent; copper ore 23 percent; and lead ore, lead-copper ore, and a little silver from placer operations, 1 percent.

Copper.—The output of recovered copper from mines in New Mexico in 1942 was 160,200,000 pounds, a 9-percent increase over the former record annual production in 1941. The Chino open-pit mine of the Kennecott Copper Corporation at Santa Rita, Grant County, continued to be by far the largest producer in the State. The capacity of the concentrator at Hurley is 18,000 tons at the desired grind and optimum metallurgy; however, the daily average quantity treated in 1942 was 20,363 tons. Copper concentrates are treated in the reverberatory furnace and converters at the company smelter at Hurley. Beginning in May 1942, part of the product was fire-refined at Hurley to 99.92-percent purity, and part continued to be cast into blister-copper anodes (99.46-percent purity) for electrolytic refining at Baltimore, Md. Other substantial copper producers in 1942 were the Burro Mountain group of the Phelps Dodge Corporation at Tyrone, Grant County; the Bonney-Anita group near Lordsburg, Hidalgo County; the Stauber mine near Pastura, Guadalupe County; and the Ground Hog-San Jose group near Hanover, Grant County. Copper ore and mine-water precipitates yielded 99 percent of the total copper; virtually all the remainder was recovered from concentrates produced by milling zinc and zinc-lead ores.

Lead.—Most of the lead produced from New Mexico mines in 1942 came from the American Smelting & Refining Co. Ground Hog mine and Hanover mill units in the Central district, Grant County. The total State output of lead was 9,216,000 pounds in 1942, compared with 9,336,000 pounds in 1941. Zinc and zinc-lead ore yielded 93 percent of the total lead, lead and lead-copper ore 4 percent, copper

ore 2 percent, and dry and siliceous ore 1 percent.

Zinc.—The output of recoverable zinc from mines in New Mexico increased 23 percent in quantity in 1942 over 1941. A substantial gain in production in the Central district, Grant County, was largely responsible for the increase. The principal producers in 1942 were the Peru Mining Co. (Pewabic and Copper Flat mines), Empire Zinc Co. (Hanover mine group), and American Smelting & Refining Co. (Ground Hog Unit), all in the Central district, Grant County; and the Ozark Smelting & Mining Co. (Waldo mine) and the Empire Zinc Co. (Kelly group), both in the Magdalena district, Socorro County. Other major zinc-producing districts were the Swartz and Pinos Altos, in Grant County; Organ, in Dona Ana County; and Lordsburg and San Simon in Hidalgo County.

Zinc concentrates produced in 1942 amounted to 99,722 tons containing, as shipped, 263 ounces of gold, 48,924 ounces of silver, 569,373 pounds of copper, 1,214,821 pounds of lead, and 107,419,144 pounds of zinc. The average zinc content was therefore 53.86 percent. The zinc and zinc-lead ores (1,049 tons) from New Mexico shipped crude

to the Ozark pigment plant at Coffeyville, Kans., averaged 19.28 percent zinc and 9.85 percent lead.

## MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in New Mexico in 1942, by counties, in terms of recovered metals

		Mines	producing	Gold (lode	and placer)	Silver (lode	and placer)
Con	$\mathbf{unty}$	Lode	Placer	Fine ounces	Value	Fine ounces	Value
Catron Colfax Dona Ana		1 3		3, 327 302 92	\$116, 445 10, 570 3, 220	210, 243 38	\$149, 506 27
GrantGuadalupe		36	21	5, 854	204, 890	298, 323	212, 141
Hidalgo Lincoln Luna Otero		6 5	8	1, 374 36 14	48, 090 1, 260 490	789 135, 045 4 339	561 96, 032 3 241
Santa Fe Sierra Socorro		4	6 12	273 612 77	9, 555 21, 420 2, 695	10 242 1, 139 29, 998	7 172 810 21, 332
Total, 1941		78 145	48 103	11, 961 27, 845	418, 635 974, 575	676, 170 1, 328, 317	480, 832 944, 581
	Cop	per	Le	ad	Zi	ne	Total
County	Pounds	Value	Pounds	Value	Pounds	Value	value
Catron Colfax		\$206	200	\$13			\$266, 170 10, 597
Dona Ana Grant Guadalupe	152, 837, 000	750   - 18, 493, 277   73, 931   -	7, 134, 000	477, 978	211,000 86,086,000	\$19, 623 8, 005, 998	23, 593 27, 394, 284 74, 492
HidalgoLin <b>c</b> oln		812, 636	292,000	19, 564	197, 000	18, 321	994, 643
Luna Otero	1,400	169	32,000 4,000	2, 144 268	32,000	2, 976	1, 263 5, 851 444
Santa Fe Sierra Socorro	300 3, 600 22, 800	36 436 2,759	11, 800 14, 000 1, 728, 000	791 938 115, 776	14, 000 12, 000 6, 370, 000	1, 302 1, 116 592, 410	11, 856 24, 720 734, 972
Total, 1941	160, 200, 000 146, 956, 000	19, 384, 200 17, 340, 808	9, 216, 000 9, 336, 000	617, 472 532, 152	92, 922, 000 75, 724, 000	8, 641, 746 5, 679, 300	29, 542, 885 25, 471, 416

Gold and silver produced at lode mines in New Mexico in 1942, by counties, in terms of recovered metals

County	Ore sold or treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	County	Ore sold or treated (short tons)	Gold (fine ounces)	Silver (fine ounces)
Catron Colfax Dona Ana Grant Guadalupe Hidalgo Luna	23, 987 1, 652 880 8, 020, 719 7, 498 126, 017	3, 327 12 92 5, 645 1, 374 14	210, 243 7 298, 271 789 135, 045 339	Otero	41 515 131 39, 950 8, 221, 512 7, 530, 226	159 14 77 10, 714 25, 357	10 239 1, 094 29, 998 676, 035 1, 328, 033

Gold and silver produced at placer mines in New Mexico in 1942, by counties, in fine ounces, in terms of recovered metals

Country	Sluicing an	d hydraulic	Dry-land	dredges 1	Total		
County	Gold	Silver	Gold	Silver	Gold	Silver	
Colfax Grant Lincoln	97 36	30 4	290 112	31 22	290 209 36	31 52 4	
Santa FeSierra	114 39	3 13	559	32	114 598	3 45	
Total, 1941	286 486	50 49	961 2,002	85 235	1, 247 2, 488	135 284	

<sup>1</sup> Dragline and power-shovel excavators with sluices or special amalgamators.

## MINING INDUSTRY

The production of ore from New Mexico mines producing gold, silver, copper, lead, and zinc totaled 8,221,512 tons in 1942, the largest in any year on record and 691,286 tons more than in 1941. Most of the output in 1942, as in 1941, was copper ore mined with power shovels from the Chino open-pit mine at Santa Rita, Grant County. The quantity of each type of ore produced, with its content in terms of recovered metals, is shown in the table that follows. Operating details at both lode and placer mines are given in the following review by counties and districts.

#### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

Ore sold or treated in New Mexico in 1942, with content in terms of recovered metals

Source	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)
Dry and siliceous gold ore. Dry and siliceous gold-silver ore Dry and siliceous silver ore	5, 718 29, 997 2, 116	1, 155 4, 112 114	4, 378 267, 298 43, 459	24, 828 8, 338	85, 713 8, 193	
	37, 831	5, 381	315, 135	33, 166	93, 906	
Copper ore. Lead ore. Lead-copper ore. Zinc ore. Zinc-lead ore.	7, 631, 752 694 618 330, 239 220, 378	4, 815 145 4 238 131	156, 613 3, 653 3, 565 144, 792 52, 277	1 159,037, 787 4, 769 42, 303 965, 684 116, 291	233, 207 208, 896 133, 420 5, 991, 636 2, 554, 935	59, 813, 725 33, 108, 275
	8, 183, 681	5, 333	360, 900	1 160,166, 834	9, 122, 094	92, 922, 000
Total, lode mines Total, placers	8, 221, 512	10, 714 1, 247	676, 035 135	1 160,200,000	9, 216, 000	92, 922, 000
Total, 1941	8, 221, 512 7, 530, 226	11, 961 27, 845	676, 170 1, 328, 317	1 160,200, 000 2 146,956, 000	9, 216, 000 9, 336, 000	92, 922, 090 75, 724, 000

<sup>&</sup>lt;sup>1</sup> Includes 26,042,745 pounds of copper recovered from precipitates from mine water and leached dumps.
<sup>2</sup> Includes 16,818,294 pounds of copper recovered from precipitates from mine water and leached dumps.

東北京 一大変のあげて あっこう

## METALLURGIC INDUSTRY

The following eight flotation mills treated 98.62 percent of the total New Mexico output of ore in 1942: Chino at Hurley, Empire Zinc at Hanover, Banner at Lordsburg, Peru near Deming, Hanover Unit near Hanover, Waldo near Magdalena, Calumet near Pinos Altos, and Southwestern near Duncan, Ariz. (operated on ore from the Carlisle group at Steeple Rock, N. Mex.). Ore shipped crude to smelters comprised 1.03 percent of the State total; and ore treated by the Little Fanney cyanidation mill at Mogollon, the East Camp cyanidation mill at Steeple Rock, and several small concentration and amalgamation mills scattered throughout the State constituted only 0.35 percent of the total. The Chino reverberatory copper smelter of the Kennecott Copper Corporation at Hurley was operated throughout 1942 on company copper concentrates, siliceous carbonate copper ore, and copper precipitates recovered by leaching of waste dumps. A substantial part of the copper production was marketed for the first time in fire-refined form. The production of copper in this form has tremendously shortened the time of refinement when compared with the time interval of shipment to Baltimore for the refining of blister copper by the electrolytic process. The gold and silver contained in the charge to the fire-refining furnace is not recovered in the operation, as would be the case in electrolytic refining. By sacrificing the gold and silver and shipping marketable refined copper direct to war material-fabricating plants (closer to New Mexico by railroad than Baltimore) much time is The destination and treatment of concentrates and ore produced by other operators in the State and shipped to smelters in other States are discussed in the following review by counties and districts. About 155,400 cubic yards of gravel were treated at three placer mines using dry-land dredges, and a quantity of gravel for which figures are not obtainable was handled at small placers worked by hand methods.

Mine production of metals in New Mexico in 1942, by methods of recovery, in terms of recovered metals

~						
Method of recovery	Material treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Ore amalgamated Ore cyanided <sup>1</sup> Concentrates smelted Ore smelted Placer	500 28, 802 337, 736 84, 352	170 3, 195 5, 652 1, 697 1, 247	42 226, 787 341, 552 107, 654 135	<sup>2</sup> 157, 754, 551 2, 445, 449	8, 614, 813 601, 187	92, 594, 946 327, 054
Total, 1941		11, 961 27, 845	676, 170 1, 328, 317	160, 200, 000 146, 956, 000	9, 216, 000 9, 336, 000	92, 922, 000 75, 724, 000

<sup>&</sup>lt;sup>1</sup> Cyanide used was approximately 151,013 pounds of Aero Brand calcium cyanide (approximately 48 to 49 percent NaCN).

<sup>2</sup> Includes 26,042,745 pounds of copper recovered from smelting of precipitates from mine water and leached

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in New Mexico in 1942, by counties, in terms of recovered metals

		Recovered	in bullion	Concentrates smelted and recovered metal					
County	Ore treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Concen- trates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	
CatronColfaxGrantSanta Fe	22, 256 1, 652 4, 944 450	2, 675 12 520 158	184, 888 7 41, 896 38						
Tota , 1941	29, 302 90, 519	3, 365 11, 067	226, 829 690, 466	84	198	780	9, 363	878	

Gross metal content of concentrates (all produced at concentrating mills) from ores mined in New Mexico in 1942, by classes of concentrates smelted

	Concen-	Gross metal content							
Class of concentrates	trates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (wet assay) (pounds)	Lead (wet assay) (pounds)	Zine (pounds)			
Dry gold	10 229, 599 2, 101 6, 304 99, 722	34 8, 110 84 556 263	72 187, 689 38, 221 129, 752 48, 924	302 1 160, 012, 157 43, 480 780, 002 569, 373	543 224, 815 2, 289, 706 6, 368, 080 1, 214, 821	232, 648 1, 358, 227 107, 419, 144			
Total, 1941 2	337, 736 313, 725	9, 047 10, 759	404, 658 518, 210	1 161, 405, 314 3 147, 911, 036	10, 097, 965 9, 480, 715	109, 010, 019 89, 017, 520			

Includes 26,596, 797 pounds of copper contained in precipitates from mine water and leached dumps.
 Includes 84 tons of concentrates from gold and silver mills containing 198 ounces of gold, 780 ounces of silvar, 9,550 pounds of copper, and 1,617 pounds of lead.
 Includes 17,185,932 pounds of copper contained in precipitates from mine water and leached dumps.

Mine production of metals from concentrating mills in New Mexico in 1942, in terms

# of recovered metals

		ВΥ	COUNT	IES			
			Conce	atrates sme	elted and recov	ered metal	
	Ore treated (short tons)	Concentrates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Dona Ana. Grant. Hidalgo. Santa Fe. Sierra. Socorro.	880 7, 944, 342 123, 762 43 99 38, 732	213 315, 982 13, 350 23 19 8, 149	92 4, 260 1, 251	220, 678 90, 763 152 831 29, 128	6, 200 1 151, 014, 644 6, 714, 339 . 300 . 3, 600 . 15, 468	6, 844, 747 254, 505 8, 354 7, 600 1, 499, 607	211, 000 86, 086, 000 144, 976 14, 000 12, 000 6, 126, 970
Total, 1941	8, 107, 858 7, 352, 950	337, 736 313, 641	5, 652 10, 559	341, 552 517, 333	1 157, 754, 551 2 144, 271, 949	8, 614, 813 8, 172, 659	92, 594, 946 75, 179, 301
	BY CLA	SSES OF	ORE C	ONCENT	RATED		
Dry and siliceous gold Copper Lead Zinc Zinc-lead Zinc-lead	3, 130 7, 555, 055 105 330, 089 219, 479	211 229, 599 15 71, 029 36, 882	477 4,806 238 131	2, 656 141, 705 122 144, 792 52, 277	22, 406 1 156, 650, 170 965, 684 116, 291	75, 378 123, 186 14, 323 5, 985, 302 2, 416, 624	59, 729, 701 32, 865, 245
	8, 107, 858	337, 736	5, 652		1 157, 754, 551		

Includes 26,042,745 pounds of copper recovered from precipitates from mine water and leached dumps.
 Includes 16,818,294 pounds of copper recovered from precipitates from mine water and leached dumps.

Gross metal content of New Mexico crude ore shipped to smelters in 1942, by classes of ore

			Gross metal content							
Class of ore	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)				
Dry and siliceous gold Dry and siliceous gold-silver Dry and siliceous silqer. Copper Lead. Lead-copper	436 2, 847 2, 116 76, 697 589 618	496 929 114 9 145	1, 673 40, 518 43, 459 14, 908 3, 531 3, 565	2, 946 9, 133 2, 454, 970 5, 890 52, 879	17, 645 14, 899 986 200, 037 216, 203 148, 244	208				
Total to copper and lead plants	83, 303	1,697	107, 654	2, 525, 818	598, 014	208				
ZincZinc-lead	150 899				9, 049 197, 588	100, 771 303, 696				
Total to zine plants	1,049				206, 637	404, 467				
Total, 1941	84, 352 86, 757	1, 697 3, 533	107, 654 119, 454	2, 525, 818 2, 759, 095	804, 651 1, 662, 961	404, 675 762, 205				

# Mine production of metals from New Mexico crude ore shipped to smelters in 1942, by counties, in terms of recovered metals

County	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Catron Grant Guadalupe Hidalgo Luna Otero Santa Fe Sierra Socorro	1, 731 71, 433 7, 498 2, 255 122 41 22 32 1, 218	652 865 123 14 1 1 13 29	25, 355 35, 697 789 44, 282 339 10 49 263 870	1,700 1,822,356 611,000 1,661 1,400	200 289, 253 37, 495 32, 000 4, 000 3, 446 6, 400 228, 393	52, <b>024</b> 32, <b>000</b> 243, <b>03</b> 0
Total, 1941	84, 352 86, 757	1, 697 3, 533	107, 654 119, 454	2, 445, 449 2, 674, 688	601, 187 1, 162, 463	327, 054 544, 699

# REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, lead, and zinc in New Mexico in 1942, by counties and districts, in terms of recovered metals

County and district	Mine	es pro- cing	Ore sold or treated (short	Gold (fine ounces)			Silver (fine ounces)			Copper (pounds)	Lead	Zinc	Total
·	Lode Placer	tons)	Lode	Placer	Total	Lode	Placer	Total	(pounds)	(pounds)	(pounds)	value	
Catron County: Mogollon Colfax County: Mount Baldy	7		23, 987 1, 652	3, 327 12	290	3, 327 302	210, 243	31	210, 243 38	1, 700	200		\$266, 170 10, 597
Dona Ana County: Organ Grant County:	3		880	92		92		91		6, 200		211,000	23, 593
Burro Mountain Central Eureka	4 11 3	1 4	736 8, 001, 808	4, 050	2 42	10 4, 092	1, 101 224, 900	14	1, 101 224, 914	7, 312, 800 145, 448, 900	47, 000 6, 411, 000	62, 600 84, 747, 200	894, 953 26, 213, 503
Pinos Altos Red Rock	6 1	16	48 720 3	178	165	343	1, 194 2, 382 4	38	1, 194 2, 420	200 11,000 400	12, 300 31, 000	79, 400	1, 697 24, 518 51
Steeple Rock Swartz White Signal	5		9, 426 7, 838	1, 390 9		1, 390 9	60, 220 8, 301		60, 220 8, 301	29, 000 24, 600	86, 700 546, 000	1, 196, 800	100, 791 157, 079
Guadalupe County	1		7, 498	10		10	169 789		169 789	10, 100 611, 000			1, 692 74, 492
ApacheLordsburg	1 2		30 123, 397	1, 257		1, 257	90, 803		90, 803	6, 715, 100	224, 400	14, 300 113, 600	1, 330 946, 693
San Simon Lincoln County: Jicarilla Luna County:	3	8	2, 590	117	36	117 36	44, 242	4	44, 242 4	900	67, 600	69, 100	46, 620 1, 263
Cooks Peak Tres Hermanas	4		17 105	14		14	97 242		97 242		11,000 21,000	32,000	1, 296 4, 555
Otero County: Sacramento Santa Fe County: Ortiz Mountains (Cerrillos)	1	5	41 65				10		10	1, 400	4,000		444
San Pedro	2 2	1	450	1 158	112 2	113 160	201 38	3	204 38	300	11, 800	14, 000	6, 229 5, 627
Chloride Hermosa	2 1		14 6	2		2	159 55		159 55		2, 600 3, 700		357 287
Kingston Las Animas (Hillsboro) Pittsburg and Caballos Mountains	1 3	3	99 11	11	582 16	593 16	831 35	44	831 79	3, 600	7, 600	12, 000	2, 687 20, 811
Tierra Blanca Socorro County: Magdalena	· 1		39, 950	77	10	<del>77</del>	14 29, 998	1	29, 998	22, 800	1,728,000	6, 370, 000	561 17 734, 972
Total New Mexico	78	48	8, 221, 512	10, 714	1, 247	11, 961	676, 035	135	676, 170	160, 200, 000	9, 216, 000	92, 922, 000	29, 542, 885

のなりを発言を表するいとう

## CATRON COUNTY

Mogollon district.—The Black Hawk Consolidated Mines Co. operated the Consolidated group and the Little Fanney 200-ton cyanide mill near Mogollon, both under lease from the Lehigh Metals Co. Operations were continuous in 1942 until June 18, at which time the Black Hawk Consolidated Mines Co. relinquished its lease on the property and disposed of all mining equipment but did not remove the mill or its equipment. In addition to ore from the Consolidated group, the mill treated custom ore from the Maude S, Champion, Little Fanney, Deep Down, and Bearup claims. Company and custom ore treated in 1942 totaled 22,256 tons, from which 2,675 fine ounces of gold and 184,888 fine ounces of silver were recovered in cyanide precipitates and refined into bullion, which was shipped to the Denver Mint. Part of the ore produced from the Bearup and Deep Down properties was shipped crude to the El Paso smelter and Ira L. Wright (ore buyer) at Silver City.

## COLFAX COUNTY

Mount Baldy district (Baldy, Elizabethtown, Eagle Nest).—Only one lode mine and one placer mine in the Mount Baldy district produced in 1942. Fullroe, Inc., worked the Grouse Gulch placer from April 1 until October 15, using a 1½-cubic yard dragline and portable screening and sluicing plant; this operation yielded most of the gold and silver produced in the district in 1942. The 50-ton cyanide plant at the Moreno-Red Bandana group, 2 miles northeast of Elizabethtown, was operated on a small scale from May 16 until November 16 by Merco, Inc. Mill feed consisted of a small tonnage of crude ore mixed with old tailings. Cyanide precipitates were shipped to the Arkansas Valley smelter at Leadville, Colo. A dragline and other equipment were installed, and a permanent sluice and jig plant was built, with accompanying water-pipe installation, during 1942 on Willow Creek near Therma, for treatment of placer gold-tungsten deposits.

## DONA ANA COUNTY

Organ district.—The quantity of ore mined and sold from the Organ district increased from 47 tons in 1941 to 880 tons in 1942. Small-scale operations at the Big Buck property produced 42 tons of crude ore, which was treated in the Hanover custom mill of the American Smelting & Refining Co. Operations at the Merrimak mine, largest producing property in the district, began in July 1942, and thereafter regular shipments of zinc-copper-lead-silver ore averaging 15 percent zinc were made to the American Smelting & Refining Co. selective-flotation zinc-lead custom mill at Hanover, Grant County. Five tons of zinc ore from the Pagoda mine also were treated in the Hanover custom mill.

## GRANT COUNTY

Burro Mountain district (Tyrone).—Throughout 1942 the Phelps Dodge Corporation continued leaching the old mine workings in situ, by percolating water and precipitating copper from the resulting copper-bearing water, at its Burro Mountain mine, 13 miles southwest of Silver City. During the year the capacity of the precipitation plant

was increased, and additional pumping facilities were installed. 'L. Yacomo and Marvin Fuller unwatered the Full Moon mine in March and began shipping zinc-lead ore to the custom mill at Hanover; small but continuous production was maintained at the property for the remainder of the year. A lessee on the Copper Sulphite claim shipped 123 tons of zinc-lead-silver ore to the Hanover custom mill for treatment. The Burro Mountain Leasing Co. worked the Thompson group of claims, beginning in August, and shipped 87 tons of oxidized copper ore to the El Paso smelter. A small-scale sluicing operation on the Paymaster placer recovered gold which was shipped to the Denver Mint.

Central district (Bayard, Fierro, Georgetown, Hanover, Santa Rita).-The Kennecott Copper Corporation Chino Mines Division, largest producer of copper in New Mexico, operated its open-pit mine at Santa Rita and flotation mill and reverberatory copper smelter at Hurley at over capacity throughout 1942. The output of copper was the largest in the history of the operation. Considerable copper was also recovered from leaching operations and from siliceous carbonate copper ore used in the converters as a flux. Additional grinding equipment was installed in the 20,000-ton concentration mill, making it possible for the mill to operate at over optimum metallurgical capacity throughout the year. Molybdenum, gold, and silver are recovered in the mill as byproducts. A substantial part of the copper was marketed for the first time in fire-refined form. Installation of a 230-foot-diameter Dorr thickening tank and a new lime-burning plant was completed, and they were put into operation early in 1942. Although drought conditions prevailed throughout the year, enough water for plant requirements was obtained through drilling additional wells and from water reclaimed from the Dorr-thickener installation.

Zinc production in the Central district in 1942 was the greatest in the history of the district. In spite of difficulties caused by governmental priorities, critical labor shortages, and marked absenteeism, which prevented maximum production, the output of recovered zinc increased 22.30 percent over 1941. Production of recovered lead, however, decreased 17.86 percent from 1941. The Peru Mining Co. expanded operations at its Copper Flat and Pewabic mines and shipped by railroad nearly 50 percent greater tonnage of ore to the company 500-ton flotation mill at Deming. Besides ore from the company properties in the Central district, the mill treated custom ore from two zinc properties in Arizona. Concentrates produced were shipped to the zinc retort plant at Dumas, Tex. Late in 1942 the company began development and search for ore in the Kearny property, which resulted favorably, and output of zinc ore began in March 1943. The Empire Zinc Co. operated its Hanover mine group and selective-flotation mill continuously in 1942 with an output virtually the same as that maintained in 1941. Maintenance of full capacity of the mill was assured only by shipment of additional ore from the company Lynchburg mine at Kelly, Socorro County. Such shipments and treatment represented a money loss. Most of the zinc concentrates produced were shipped to the New Jersey Zinc Co. plant at Depue, Ill. (Mineral Point Zinc Division); byproduct lead concentrates made were shipped to the El Paso smelter. Production of zinc concentrates from the Hanover milling unit (formerly Combination-Black Hawk mill), operated under lease by the American

The state of the s

Smelting & Refining Co., was nearly two-thirds greater than in 1941. Most of the ore treated came from the company Ground Hog-San Jose group, which produced in addition to zinc-lead-copper-silver milling ore a small tonnage of lead-copper-silver-gold ore, which was shipped crude to the El Paso smelter. About 22 percent of the total ore milled was custom ore from the Combination, Hobo, Free Gold, Barringer, and Peerless properties in the Central district; the Columbia, Grandview, and Royal John claims in the Swartz (Carpenter) district; the Manhattan and Baldback mines in the Pinos Altos district; the Copper Sulphite and Full Moon properties in the Burro Mountain (Tyrone) district; the Big Buck, Merrimak, and Pagoda mines near Organ; the Ruth mine near Lordsburg; the Silver Hill property near Steins; the Percha mine near Kingston; and the Nitt and El Tigre properties near Magdalena. Several small shipments of crude ore were made to the El Paso smelter from the Little Goat and the Georgetown Extension group at Hanover.

Late in 1941 the United States Smelting, Refining & Mining Co. began acquiring, under lease and option, a number of claims in the vicinity of Vanadium, which it later consolidated into what is now known as the Bullfrog mine. Development and exploration at this mine were carried on throughout the year and consisted of a new 626-foot shaft, 2,938 feet of drifts, 23,618 feet of diamond-drill holes, construction of a steel headframe, shops, office, and warehouse. In July 1942 a contract was let for the construction of a 250-ton selective-flotation mill adjacent to the mine. Difficulty in obtaining equipment and carpenters retarded the normal construction progress, so that the mill was not completed and put into operation until March 1943. Mill feed for the first few months of operation consisted of ore (from development and exploration) that had been stock-piled at the mine. It is expected that this operation will add materially

to the production of zinc in the Central district.

Ground sluicing of dry-wash gravels in Gold Gulch by prospectors

and vacationists recovered a little placer gold.

Eureka district.—Intermittent small-scale operations at the Hornet and Bonanza properties produced small lots of lead ore, which were shipped crude to the El Paso smelter or sold to Ira L. Wright, ore

sampler and purchaser, at Silver City.

Pinos Altos district.—A lessee operating intermittently the 20-ton Calumet mill 1 mile south of Pinos Altos treated zinc-lead-bearing tailings reported from the Cleveland dump and shipped zinc and lead concentrates to the Amarillo and El Paso smelters. Lessees on the Baldback and Manhattan mines shipped crude zinc-lead-copper-gold-silver ore to the Hanover custom mill. Gold-silver-copper-lead and gold-silver-copper ores were shipped in small lots to the El Paso smelter and Ira L. Wright from the Blue Jay, Buckhorn, and Langston prospects in the Pinos Altos district. Virtually all the placer gold from the district in 1942 was recovered by Cooperative Placers, which operated a dragline land dredge in Santo Domingo Gulch until April. Numerous small placers, usually operated after flash showers and cloudbursts that reworked the gulch gravels, were continued throughout the year by residents of the community.

Red Rock district.—Three tons of copper-silver ore were shipped

in 1942 from the Fence claim in the Red Rock district.

Steeple Rock district.—The Southwestern Mineral Co. worked the Center claim and Carlisle dump in 1942 from January 1 until June 30 and produced 3,459 tons of gold-silver-copper-lead ore, of which 3,130 tons were concentrated in the company 100-ton flotation mill at Duncan, Ariz., and 329 tons were shipped crude to the El Paso Plans were being made early in 1943 to reopen the property smelter. for the production of zinc and lead. Reserves are estimated at 100,000 tons of 5-percent zinc, 2-percent lead, and 4½-percent copper. The Exploration Syndicate, Inc., continued to operate the East Camp group until April 1942. All the ore produced was treated in the company 75-ton cyanide mill at the mine; the gold-silver bullion recovered was shipped to the Denver Mint. Flotation cells were added to the mill late in 1942, and the company plans to produce zinc concentrates from East Camp ore in 1943. Small shipments of crude ore were made to the International Smelting & Refining Co. smelter at Miami. Ariz., from the Laura, Norman King, and Ontario properties.

Swartz (or Carpenter or Camp Monarch) district.—The Black Range Development Co. reopened the Grandview and Columbia properties in February 1942 and produced 6,893 tons of zinc-lead-silver ore, which was trucked to the Hanover custom mill. A. L. Owen shipped zinc-lead-silver ore regularly from the Royal John mine to the Hanover

custom mill.

White Signal district.—A shipment of 128 tons of crude smelting ore reported to be from the True Blue claim was made in 1942. Other activities in the White Signal district consisted of two one-man operations that produced small lots of crude ore which were sold to Ira L. Wright at Silver City. Production came from the Big Chief and Combination prospects.

#### GUADALUPE COUNTY

The Stauber mine near Pastura was operated under lease in 1942 from January to June 31 by Alex Bonnyman, Jr., and the remainder of the year by the Guadalupe Mining Co. Shipments to the El Paso smelter for the year amounted to 7,498 tons of siliceous copper ore averaging 4.24 percent copper and 0.105 ounce of silver to the ton.

## HIDALGO COUNTY

Apache district.—A lessee operating the Apache group shipped 1 carload of zinc smelting ore averaging 30 percent zinc to the Ozark Smelting & Mining Co. leaded-zinc pigment plant at Coffeyville, Kans.

Lordsburg district.—The Banner Mining Co., second-largest producer of copper in New Mexico, operated the Bonney and Anita No. 1 mines and a 500-ton flotation mill, 6 miles south of Lordsburg, continuously throughout 1942. Ore produced from the various levels of the mine is hoisted through a 1,475-foot, vertical, three-compartment main shaft situated 100 feet from the mill. Copper-gold-silver concentrates were sold to the El Paso smelter. Production from the old Anita mine, 5 miles south of Lordsburg, was started early in 1942 following an intensive rehabilitation and development program, which consisted in unwatering the mine, reconditioning the 800-foot shaft, diamond drilling 297 feet of exploratory drill holes, and driving 130

feet of raise and 43 feet of winze. The ore was trucked to the Banner mill at the Bonney mine for treatment. Development at the Bonney mine consisted of 2,744 feet of exploratory diamond drilling, sinking 126 feet of shaft, and driving 2,607 feet of drift. The National Zinc Corporation obtained a lease on the Ruth property and began shipping crude zinc-lead sulfide ore on April 4 to the Hanover custom mill (Grant County). Operations were continued throughout the year. Exploration and development comprised sinking 165 feet of shaft and driving 585 feet of drift. In 1943 an experimental 50-ton gravityconcentration pilot plant was installed on the Ruth property. If the metallurgical results of the pilot plant are satisfactory, the National Zinc Corporation plans to construct a larger mill for treating the Ruth ore.

The Federal Bureau of Mines late in 1942 and early in 1943 explored by diamond drilling at the Atwood group of claims on Atwood Hill near Valedon, 4 miles south of Lordsburg, in addition to rehabilitating the Henry Clay shaft on the property. If Bureau findings are satisfactory, active mining probably will be done on this property in 1943.

San Simon (Steins) district.—The Byrd Mining Co. operated, under lease, the Silver Hill property 9 miles south of Steins and began regular carload shipments of zinc-lead sulfide ore to the Hanover custom mill (Grant County) in May. Ore shipped averaged 8.14 percent lead, 3.26 percent zinc, and 1.86 ounces of silver to the ton. The Shattuck-Denn Mining Co. acquired the McGhee mine under a long-term lease late in November and began renovating equipment and buildings preparatory to production of ore. It is planned to treat the ore in the Shattuck-Denn custom mill at Bisbee, Ariz. The Diamond Mining Co. operated the Volcano group, 6 miles north of Steins, from April 1 to November 1 and shipped 2,115 tons of dry silver ore to the Miami (Ariz.) smelter. Small lots of crude smelting ore were shipped from the Carbon Hill and Central mines.

## LINCOLN COUNTY

Jicarilla district.—All the output from the Jicarilla district and Lincoln County in 1942 was in small lots of placer gold recovered from stream gravels in the Jicarilla Mountains southeast of Ancho. The gold produced was sold to merchants in Ancho and Jicarilla.

## LUNA COUNTY

Cooks Peak district.—Small tonnages of lead-silver ore were shipped through Ira L. Wright at Silver City in 1942 from the "85"-Ethel group, Lookout, Mickey, Surprise, and Mahoney Shaft No. 1 properties.

Deming district.—The Peru Mining Co. operated continuously in 1942, at slightly over capacity, its 500-ton selective-flotation mill at Wemple, near Deming. Most of the ore treated was moved by railroad from the company-operated Pewabic and Copper Flat mines in the Central district (Grant County). Some custom ore from two zinc properties in Arizona also was treated. The output of zinc concentrates increased nearly 50 percent over 1941.

## OTERO COUNTY

Sacramento district.—I. W. Morrison shipped 41 tons of lead-coppersilver ore to the El Paso smelter from the Warwick claim in 1942.

## SANTA FE COUNTY

Ortiz Mountains (Cerrillos) district.—Development and exploration on the Mina de Tira property 2½ miles north of Cerrillos produced 22 tons of lead-silver-copper-gold ore, which was shipped to the El Paso smelter. The Cerrillos Lead & Zinc Co. operated under lease the Pennsylvania mine, 12 miles northwest of Cerrillos, during the last 3 months of 1942 and shipped 43 tons of zinc-lead-silver ore to the Hanover custom mill (Grant County). Sluicing stream gravels on the Ortiz Grant southeast of Cerrillos recovered small lots of placer gold.

San Pedro or New Placers district.—A lessee worked the Candelari mine on a small scale and trucked the ore produced 4 miles to his 10-ton amalgamation mill at Golden for treatment. At the Old Timer mine, near Golden, 100 tons of ore were mined and treated in a Huntington mill. Several individuals continued to sluice placer gravels in

the vicinity of Golden.

## SIERRA COUNTY

Chloride (Apache, Cuchillo Negro) district.—The only producing properties in the Chloride district in 1942 were the Apache group and the Minnehaha claim, from which small lots of smelting ore were shipped direct to the El Paso smelter or through Ira L. Wright at Silver City.

Hermosa district.—The only output from the Hermosa district in

1942 was 6 tons of lead-silver ore from the Pelican group.

Kingston district.—A lessee on the Percha mine in the Black Range west of Kingston operated part of 1942 and shipped 99 tons of zinclead-copper-silver ore to the Hanover custom mill in Grant County for treatment.

Las Animas district (Hillsboro).—Intermittent small-scale operations on the Tresness, Nicolds, and Wicks claims in the Las Animas district produced several lots of smelting ore, which were shipped to the El

Paso smelter or to Ira L. Wright at Silver City.

The John I. Hallett Construction Co. continued operations in 1942 until November 15 at the leased Gold Dust, Graf Von Luxemburg, Bunker Hill, and other placers in a group about 8 miles east of Hillsboro. The equipment consists of two gasoline-powered dragline excavators of 1- and 1½-cubic yard capacity, a Coulter-Ainlay bowl recovery plant mounted on wheels, water-storage tanks, and pumps. Sluicing and panning at other placers in the Las Animas district recovered small lots of gold.


Pittsburg and Caballos Mountains district.—Itinerant prospectors panned for gold in 1942 on the stream gravels of the Pittsburg and Caballos Mountains district and sold what gold they recovered to the

Myers Co. store at Hatch.

Tierra Blanca district.—L. E. Cleveland shipped 1 ton of lead-silver smelting ore from his Silver Bell claim through Ira L. Wright, ore buyer, at Silver City.

#### SOCORRO COUNTY

Magdalena district.—Production of recoverable zinc from the Magdalena district increased from 5,159,000 pounds in 1941 to 6,370,000 pounds in 1942, or 23.47 percent; the output of recovered lead increased from 847.400 to 1.728,000 pounds, or 103.92 percent. Raskob Mining Interests, Inc., continued to operate, under lease and option, the Waldo mine and 200-ton flotation mill until July 1, when it relinguished the lease and the property reverted to the owners, the Sherwin-Williams Co. The property remained idle until October 1942, when the Ozark Smelting & Mining Co., (subsidiary of the Sherwin-Williams Co.) resumed production and continued to operate the mine and mill the remainder of the year. Ore milled during 1942 by both operators totaled 29,118 tons, yielding 4,012 tons of zinc concentrates and 291 tons of lead concentrates. The ore milled contained traces of gold, silver, and copper and averaged 2.8 percent lead and 12.7 percent zinc. The concentrates produced were shipped to the Ozark Smelting & Mining Co. pigment plant at Coffeyville, Kans., the El Paso smelter, and the Dumas smelter of the American Zinc Co. of Illinois. On April 10, 1943, the Waldo property (mine and mill) was purchased by the American Smelting & Refining Co., which continued operations. The Kelly Unit (Lynchburg and Kelly mines) of the Empire Zinc Co. was worked by lessees, who shipped zinc-lead ore to the Empire Zinc Co. flotation mill at Hanover and to the Ozark Smelting & Mining Co. pigment plant at Coffeyville, Kans. Victor Papa shipped 267 tons of lead-copper-silver-gold ore from the West Star property to the El Paso smelter. J. A. McDonald began operations on the Nitt claim in August and shipped crude zinclead-silver ore to the Hanover custom mill (Grant County) in addition to making several shipments of copper-silver ore to the El Paso smelter. A lessee on the El Tigre mine shipped 1 carload of zinclead ore to the Hanover custom mill.



# GOLD, SILVER, COPPER, LEAD, AND ZINC IN OREGON

(MINE REPORT)

By CHARLES WHITE MERRILL AND H. M. GAYLORD

## SUMMARY OUTLINE

	Page		Page
Summary	457	Mining industry—Continued.	
Calculation of value of metal production	458	Ore classification	462
Mine production by counties.	460	Metallurgic industry	461
Mining industry	461	Review by counties and districts	465

## SUMMARY

The gold-mining industry of Oregon collapsed during 1942. In 1940 gold production reached an all-time high, but by the end of 1942 the few mines with substantial gold output in the earlier months of the year had suspended operations. Silver and lead production also decreased in both quantity and value, and the small rise in copper output was not significant in the State total for the four metals.

The total value of the gold, silver, copper, and lead (in terms of recovered metals) produced in Oregon was \$1,708,297 in 1942 compared with \$3,602,468 in 1941. It was divided among the metals as follows: Gold, 95 percent; silver, 4 percent; and copper and lead combined, 1 percent. No recovery of zinc has been reported since 1937. Baker County continued to be the leading metal producer and contributed 40 percent of the State total value; Grant County yielded 27 percent, Jackson County 18 percent, Josephine County 7 percent, and the other eight producing counties 8 percent. Distribution of production, by counties, was much the same as in 1941.

Rising wages, enlistment of miners in the armed forces, migration of miners to war industries, rising costs of supplies and equipment and the difficulties of obtaining them, higher taxes, and a fixed price for gold and silver (principal metals produced in the State) were factors that continued to crush the industry in 1942 as in 1941. When the War Production Board issued Order L-208 October 8, production, which had already sunk to approximately one-third of its 1940 level, quickly collapsed. The five leading gold producers for the year 1942 suspended operations between October 7 and 31; they supplied 50 percent of the State output.

Lode mines were affected sooner than placers, so that only 17 percent of the total gold in 1942 came from lodes. For a number of years lode mines had produced about one-third and placers two-thirds of the gold output.

All tonnage figures are short tons and "dry weight"; that is, they

do not include moisture.

Yardage figures used in measuring material treated in placer

556250—43——30

457

operations are bank measure; that is, the material is measured in the ground before treatment.

The value of metal production herein reported has been calculated at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zine 4
1938. 1939. 1940. 1941.	Per fine ounce \$35.00 35.00 35.00 35.00	Per fine ounce \$ \$0.646+ 6.678+ 7.711+ 7.711+ 7.711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057	\$0.048 .052

Mine production of gold, silver, copper, lead, and zinc in Oregon, 1938-42, and total, 1852-1942, in terms of recovered metals

Year	Mines producing 1		Ore, old	Gold (lode and placer)		Silver (lode and placer)	
	Lode	Placer	tailings, etc. (short tons)	Fine ounces	Value	Fine ounces	Value
1938 1939 1940 1941 1942	84 116 112 91 48	157 201 192 153 83	74, 936 69, 025 105, 469 98, 160 31, 728	81, 729 93, 372 113, 402 96, 565 46, 233	\$2, 860, 515 3, 268, 020 3, 969, 070 3, 379, 775 1, 618, 155	100, 507 105, 388 219, 112 276, 158 87, 376	\$64, 974 71, 536 155, 813 196, 379 62, 134
1852-1942			(2)	5, 667, 021	126, 308, 778	5, 177, 158	4, 759, 521
					1		1
	Cop	per	Le	ad	Zi	ne	
Year	Cop	per Value	Le Pounds	ad Value	Zi	ne Value	Total value
Year  1938 1939 1940 1941 1942							Total value \$2, 935, 053 3, 350, 950 4, 148, 271 3, 602, 468 1, 708, 297

<sup>1</sup> Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to

¹ Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.

¹ Treasury buying price for newly mined silver.

¹ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.

¹ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.

¹ \$0.64646464.

¹ \$0.67878787.

ʔ \$0.711111111.

property.
Figures not available. 3 Short tons.

Gold produced at placer mines in Oregon, 1938-42, by classes of mines and by methods of recovery

	352	Material treated (cubic yards)	Gold recovered		
Class and method	Mines pro- ducing 1		Fine ounces	Value	Average per cubic yard
Grand and all and a second					
Surface placers: Gravel mechanically handled: Connected-bucket dredges:					
1938	5	7, 258, 000 6, 267, 000 7, 580, 000	29,006	\$1, 015, 210 875, 980	\$0.140
1939	5	6, 267, 000	25,028	875, 980	. 140
1940	6 7	7, 580, 000	24, 951	873, 285	.118
1941 1942	6	6, 670, 000 4, 725, 000	24, 131 21, 641	844, 585 757, 435	160
Dragline dredges: 2					
1938	11	2, 891, 000	15, 939 26, 257	557, 865	. 193
1939	10	5, 964, 000	26, 257	918, 995	.154
. 1940	23 25	7, 301, 000	99 205	1, 232, 560 993, 825	. 167
1941 1942	14	2,891,000 5,964,000 7,361,000 6,256,000 2,852,000	35, 216 28, 395 13, 383	468, 405	. 164
Suction dredges: 3				0.00	046
1941	1	27, 000	191	6, 685	. 248
1942			=====		=====
Nonfloating washing plants: 4		136,000	1 760	61, 880	. 456
1938	5 13	346, 000	1,768 2,169	75, 915	. 219
1940	20	638, 000	4, 092	143 220	. 224
1941	29 17	567, 000	2, 757	96, 495	.170
1942	6	45, 000	380	13, 300	. 296
Gravel hydraulically handled:					
Hydraulie:				444 400	
1938	66	731, 000	3,261	114, 135	.156
1939	76 82	440, 000 599, 000	2, 585 2, 731	90, 475 95, 585	.160
1940	63	683, 000	2, 306	80, 710	.118
1941 1942	41	306,000	1,420	49, 700	. 162
Small-scale hand methods: 8					
Wet:					405
1938	57	332, 800	3,874	135, 990	.407
1939	83 44	299, 200 499, 300	4, 398 4, 279	100, 900	300
1940	33	438, 300	2, 553	89 355	204
1941 1942	12	220, 500	1, 462	135, 590 153, 930 149, 765 89, 355 51, 170	. 235
Dry:					
1938	2	800	16	560	.700
1939	1	400	13	455	1. 139
1940	1	500	21	735	1.470 1.050
1941	1	100	3	105	1.050
1942					
Underground placers: Drift:					
1938	11	5, 400	467	16, 345	3.02
1939	13	5, 400	329	11, 515	2. 13
1940	10	6, 200	287	10, 045	1.62
1941 1942	6 4	4, 600 1, 500	94 50	3, 290 1, 750	. 71. 1. 16
Grand total placer:					
1939	157	11, 355, 000	54, 331 60, 779 71, 577	1, 901, 585 2, 127, 265 2, 505, 195	. 16
1939	201	13, 322, 000 16, 684, 000	60,779	2, 127, 265	160
10/1		14,646,000	60, 430	2, 115, 050	.14
		8, 150, 000	38, 336	1, 341, 760	.16
1940 1941 1942	6 192 153 83	16, 684, 000 14, 646, 000 8, 150, 000	71, 577 60, 430 38, 336	2, 505, 195 2, 115, 050 1, 341, 760	

Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to

<sup>\*</sup> Excludes timerant prospectors, simpers, ingregaters, and others who gave no evidence of legal right to property.

\* Includes all placer operations using dragline excavator for delivering gravel to floating washing plant.

\* Includes all placer operations using suction pump for delivering gravel to floating washing plant, except those producing less than 100 ounces of gold, which are included under "Small-scale hand methods"; no suction dredges reported for 1938-40, inclusive, and 1942.

\* Includes all placer operations using power excavator and washing plant, both on dry land; when washing plant is movable, outfit is termed "dry-land dredge."

\* Includes all operations in which hand labor is principal factor in delivering gravel to sluices, long toms, din hores, page, etc.

dip boxes, pans, etc.

• A mine using more than 1 method of recovery is counted but once in arriving at total for all methods.

Gold.—Production of gold in Oregon in 1942 decreased 52 percent compared with 1941—the output from placers 37 percent and that from lode mines 78 percent. Of the total placer gold, connectedbucket dredges recovered 56 percent, dragline dredges 35 percent, hydraulicking and small-scale hand methods 4 percent each, and nonfloating washing plants (with mechanical excavators) and drift mines 1 percent. Virtually all the lode gold was derived from dry ores and most (96 percent) of it from dry gold ore. Although 131 properties produced in 1942, the bulk of the gold came from relatively few mines; the following 10 properties, listed in order of output, supplied 71 percent of the State total: Sumpter Valley Dredging Co. (connected-buckét dredge), Porter & Co. (connected-bucket dredge), Stearns & Owens (Kubli operation) (dragline dredge), Ferris Mining Co. (dragline dredge), Sunshine Mining Co. (Burnt River Division) (connected-bucket dredge), Timms Gold Dredging Co. (connectedbucket dredge), Ellis Mining Co. (gold ore), Stearns & Owens (Alaska of Oregon operation) (dragline dredge), Western Gold Dredging Co. (connected-bucket dredge), and Consuelo Oregon Mines (dragline dredge). Only one of the 10 is a lode mine.

Silver.—Silver production in Oregon in 1942 decreased 68 percent compared with 1941. Of the State total, Jefferson County yielded almost two-thirds, and most of the remainder came from Lane and Baker Counties; dry silver ore yielded 45 percent, dry gold ore 27 percent, dry gold-silver ore 20 percent, and placer gravels almost all the rest. Smelting of crude ore accounted for 59 percent of the total lode silver and smelting of concentrates for virtually all the rest.

Copper, lead, and zinc.—Most of the copper output of Oregon in 1942 was a byproduct of ores worked primarily for their gold content. The lead output of the State, which totaled only 46,000 pounds, was derived entirely from precious-metal ores. No zinc was reported recovered.

#### MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, and lead in Oregon in 1942, by counties, in terms of recovered metals

	Mines pr	oducing 1		Gold									
County				ode	Pla	acer	Total						
	Lode	Placer	Fine ounces	Value	Fine ounces	Value	Fine ounces	Value					
BakerCoosCurryDouglas.	11	(²) 11 2 5	2, 731	\$95, 585	16, 455 17 28	\$575, 925 595 980	19, 186 17 28	\$671, 510 595 980					
Grant Harney	7	(2) 15	1, 502	455 52, 570	97 11, 541 6	3, 395 403, 935 210	110 13, 043 6	3, 850 456, 505 210					
Jackson Josephine Malheur Union	14 12	17 29 3	354 1,859	12, 390 65, 065	8, 423 1, 521 247	294, 805 53, 235 8, 645 35	8, 777 3, 380 247	307, 195 118, 300 8, 645 35					
Other counties 3	3		1,438	50, 330			1, 438	50, 330					
Total, 1941	48 91	83 153	7, 897 36, 135	276, 395 1, 264, 725		1, 341, 760 2, 115, 050	46, 233 96, 565	1, 618, 155 3, 379, 775					

See footnotes at end of table.

Mine production of gold, silver, copper, and lead in Oregon in 1942, by counties, in terms of recovered metals—Continued

County		lode and cer)4	Cor	per	Le	Total	
County	Fine ounces	Value	Pounds	Value	Pounds	Value	value
Baker Coos Curry	10, 959 7 7	\$7,793 5 5	6, 000	\$726	3		\$680, 029 600 985
Douglas Grant Harney	24 4, 936	17 3, 510	4,000	484			3, 867 460, 499 210
Jackson Josephine Malheur	1,336 526 38	950 374 27	16,000	1,936	2,000	\$134	308, 279 120, 610 8, 672
UnionOther counties 3	69, 543	49, 453	180,000	21, 780	44,000	2, 948	35 124, 511
Total, 1941	87, 376 276, 158	62, 134 196, 379	206, 000 166, 000	24, 926 19, 588	46, 000 118, 000	3, 082 6, 726	1, 708, 297 3, 602, 468

<sup>1</sup> Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to

#### MINING INDUSTRY

Of the 31,728 tons of ore (including 3,075 tons of old tailings) sold or treated in Oregon in 1942, Lane County produced 12,442 tons or 39 percent, Baker County 6,623 tons (including 2,500 tons of old tailings) or 21 percent, Josephine County 4,795 tons or 15 percent, Grant County 4,721 tons or 15 percent, and Jefferson County 2,615 tons (including 400 tons of old tailings) or 8 percent. Almost 92 percent of the ore (including old tailings) was dry gold ore, and virtually all the remainder was dry gold-silver and silver ore.

The six properties worked by connected-bucket dredges had one dredge each, none of which worked at more than one property in 1942; at the end of the year all operations had been suspended. dragline dredges washed gravel at 14 Oregon properties, but none was in operation at the close of the year; the dragline excavators were equipped as follows: 3 each with 2- and 11/4-cubic yard buckets

and 1 each with a 3-, 2½-, 1¾-, and 1½-cubic yard bucket.

Reports on the use of quicksilver at Oregon placer mines indicate that 867 pounds were consumed during 1942. The placer operators reporting on quicksilver consumption furnished 1942 data from which the following quantities of gold recovered per pound of quicksilver consumed have been calculated (1941 figures in parentheses): Connected-bucket dredges, 37 ounces of gold per pound of quick-silver (none in 1941); dragline dredges, 76 ounces (55); hydraulic mines, 30 ounces (21); and small-scale hand operations, 27 ounces (6).

#### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

property.

2 Output from property not classed as a "mine."

3 Jefferson and Lane Counties.

4 Sources of total silver as follows—1942: 80,235 ounces from lode mines and 7,141 ounces from placers; 1941: 284,953 ounces from lode mines and 11,205 ounces from placers.

Ore and old tailings sold or treated in Oregon in 1942, with content in terms of recovered metals

		al sold or ated				
Source	Ore	Old tail-	Gold	Silver	Copper	Lead
Dry and siliceous gold ore	Short tons 26, 380 1, 180 1, 035 58	Short tons 2,675 400	Fine ounces 7, 562 131 202 2	Fine ounces 23, 421 17, 338 39, 459 17	Pounds 176, 600 5, 500 8, 500 15, 400	Pounds 26,000 10,300 9,700
Total, lode mines Total, placers	28, 653	3, 075	7, 897 38. 336	80, 235 7, 141	206,000	46, 000
Total, 1941	28, 653 96, 975	3, 075 1, 185	46, 233 96, 565	87, 376 276, 158	206, 000 166, 000	46, 000 118, 000

#### METALLURGIC INDUSTRY

Of the State total ore and old tailings (31,728 tons), 58 percent was treated in concentrating mills, most of which used flotation; 23 percent was treated in amalgamation and cyanidation mills, with or without concentration equipment; and 19 percent was shipped crude to smelters. Ultimate recovery of 50 percent of the total lode gold was from the smelting of ore; 29 percent from the smelting of concentrates; 16 percent as bullion from cyanidation of ore and old tailings; and 5 percent as bullion from amalgamation of ore. All material requiring smelting was shipped out of the State, as Oregon has no smelters.

Data furnished by operators of some of the gold and silver mills show that 4,003 pounds of 91-percent sodium cyanide were consumed in recovering 1,235 ounces of gold and 198 ounces of silver from 4,213 tons of ore and 2,500 tons of old tailings, and that 21 pounds of quick-silver were used in recovering 170 ounces of gold and 44 ounces of silver from 278 tons of ore.

Mine production of metals in Oregon in 1942, by methods of recovery, in terms of recovered metals

Method of recovery	Material treated	Gold	Silver	Copper	Lead
Ore and old tailings amalgamated	Short tons 565	Fine ounces 437	Fine ounces 95	Pounds	Pounds
Ore and old tailings cyanided Concentrates smelted: Flotation	6,838 1,420	1, 246 2, 246	204 32, 421	172, 400	36, 300
GravityOre smelted	5, 977	3, 951	10 47, 505	33, 600	9, 700
Total, lode mines Total, placers		7, 897 38, 336	80, 235 7, 141	206, 000	46, 000
Total, 1941		46, 233 96, 565	87, 376 276, 158	206, 000 166, 000	46, 000 118, 000

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in Oregon in 1942, by types of mills and by counties, in terms of recovered metals

#### AMALGAMATION MILLS

	Materia	l treated	Recovered	in bullion	Concentrates smelted and recovered metal					
County	Ore i	Old tail- ings	Gold	Silver	Concen- trates produced	Gold	Silver			
BakerGrant	Short tons 190 54	Short tons	Fine ounces 112 56	Fine ounces	Short tons	Fine ounces 2	Fine ounces			
Jackson Josephine	90 181	50	116 153	12 32 22	<u>ž</u>	<u>i</u> ī-				
Total, 1941	515 1, 440	50	437 971	95 222	3 12	13 62	1 21			
		CY	ANIDATIO	N MILLS						
Baker Jackson Josephine	4, 213	2, 625	1, 246	204						
Potal, 1941	4, 213 21, 617	2, 625 1, 185	1, 246 4, 056	204 513						
Grand total: 1942	4, 728 23, 057	2, 675 1, 185	1, 683 5, <b>027</b>	299 735	3 12	13 62	1 21			

<sup>&</sup>lt;sup>1</sup> Figures under "Ore" for cyanidation mills include both raw ore and concentrates cyanided but not raw ore concentrated before cyanidation of concentrates.

## Mine production of metals from concentrating mills in Oregon in 1942, by counties, in terms of recovered metals

	c	Concentrates smelted and recovered metal							
County	Ore	Old tail- ings	Concen- trates produced	Gold	Silver	Copper	Lead		
Baker	Short tons	Short tons	Short tons	Fine ounces	Fine ounces	Pounds	Pounds		
GrantOther counties !	4, 090 13, 846	400	468 952	990 1, 256	2, 234 30, 187	900 171, 500	36, 300		
Total, 1941	17, 948 65, 130	400	1, 421 6, 363	2, 250 25, 534	32, 430 161, 305	172, 400 112, 200	36, 300 84, 000		

Jackson, Jefferson, and Lane Counties.

## Gross metal content of concentrates produced from ores mined in Oregon in 1942, by classes of concentrates

Class of concentrates	Concen-		Gross metal content								
	trates	Gold	Silver	Copper	Lead	Zine					
Dry gold	Short tons 472 261 659 32	Fine ounces 1,007 131 771 354	Fine ounces 2, 244 17, 338 12, 291 558	Pounds 1, 402 5, 815 169, 419 1, 667	Pounds 1, 022 14, 185 35, 656 6, 925	Pounds 18, 103					
Total, 1941	1, 424 6, 375	2, 263 25, 596	32, 431 161, 326	178, 303 117, 114	57, 788 109, 295	18, 10 79, 42					

# Mine production of metals from Oregon concentrates shipped to smelters in 1942, in terms of recovered metals BY COUNTIES

	Concentrates	Gold	Silver	Copper	Lead
	Short tons	Fine ounces	Fine ounces	Pounds	Pounds
Baker Grant Jackson	468 11 2	990 40	2, 234 156	900	2,000
Josephine Other counties 1	941	11 1, 216	30, 031	171, 500	34, 300
Total, 1941	1, 424 6, 375	2, 263 25, 596	32, 431 161, 326	172, 400 112, 200	36, 300 84, 000
	BY CLASSES	OF CONCE	NTRATES		
Dry gold	472 261 659 32	1, 007 131 771 354	2, 244 17, 338 12, 291 558	900 5, 500 165, 000 1, 000	10, 300 19, 600 6, 400
	1, 424	2, 263	32, 431	172, 400	36, 300

<sup>1</sup> Jefferson and Lane Counties.

### Gross metal content of Oregon crude ore shipped to smelters in 1942, by classes of ore

Class of ore	Ore	Gold	Silver	Copper	Lead
Dry and siliceous gold Dry and siliceous silver Copper	Short tons 4, 884 1, 035 58	Fine ounces 3,747 202 2	Fine ounces 8,029 39,459 17	Pounds 10, 734 9, 742 16, 014	Pounds 1, 419 17, 566
Total, 1941	5, 977 8, 896	3, 951 5, 512	47, 505 102, 892	36, 490 58, 265	18, 985 64, 936

## Mine production of metals from Oregon crude ore shipped to smelters in 1942, in terms of recovered metals

#### BY COUNTIES

	Ore	Gold	Silver	Copper	Lead
Baker	Short tons 3, 921	Fine ounces 2, 414 13	Fine ounces 6, 969 10	Pounds 6,000	Pounds
Douglas Grant Josephine Other counties 1	8 577 401 1, 070	456 659 409	679 297 39, 550	3, 100 16, 000 8, 500	9,700
Total, 1941	5, 977 8, 896	3, 951 5, 512	47, 505 102, 892	33, 600 53, 800	9, 700 34, 000
	BY CL	ASSES OF O	RE		
Dry and siliceous gold	4, 884 1, 035 58	3, 747 202 2	8, 029 39, 459 17	9, 700 8, 500 15, 400	9, 700
Ī	5, 977	3,951	47, 505	33, 600	9, 700

<sup>1</sup> Jackson, Jefferson, and Lane Counties.

## REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, and lead in Oregon in 1942, by counties and districts, in terms of recovered metals 1

County and district 1	Mines pr	oducing 2	Ore and		Gold		Silver				GOLD
County and district.	Lode	Placer	old tailings	Lode	Placer	Total	(lode and placer) <sup>8</sup>	Copper	Lead	Total value	D, 8
Baker County: Baker	2	(4)	Short tons 257	Fine ounces	(4)	5 120	Fine ounces 5 661	Pounds	Pounds	<sup>5</sup> \$4, 670	SILVER
Connor Creek	3	1 3	3, 548	2, 206	2, 925	72 2, 206 2, 925	6, 151 578			2, 525 82, 310 102, 786	_
Mormon Basin 7		3	72	17	13, 087	104 17 13, 087	31 14 3, 143			3, 662 605 460, 280	COPPER
Virtue		(8)	2, 725 21	331 57	39	54 331 96	308 21			1, 895 11, 804 3, 375	ER,
Coos Bay Coquille. Curry County;		(8) (8)			9 8	9 8	3 4			317 283	LEAD
Chetco Gold Beach Sixes		(8) 1			10 10 14	10 14	3			140 352 493	
Douglas County: Riddle		5	8	13	97	97 13	14 10			3, 405 462	AND
Grant County: Canyon. Granite. Greenhorn <sup>6</sup> North Fork John Day	1 2	(4) 5 2	3 4, 551 166	3 1,291 206	4, 912 (4) 2, 442 126	4, 915 5 1, 291 2, 648 126	488 5 2, 423 959 28	1, 600 <b>2, 4</b> 00		172, 372 5 47, 102 93, 652 4, 430	ZINC
Quartzburg Susanville Harney County: Idol City Jackson County:	1	(8)	1	2	13 31 6	15 15 31 6	28 3 7			527 1,090 210	IN OR
Ashland. Gold Hill. Jacksonville. Upper Applegate.	2 5 3 2	6 3 8	191 57 16	6 92 8 26	4, 046 310 4, 067	4, 138 318 4, 093	526 52 564			210 145, 204 11, 167 143, 656	OREGON

See footnotes at end of table.

	Mines p		Ore and		Gold		Silver	G		
County and district	Lode	Placer	old tailings	Lode	Placer	Total	(lode and placer)	Copper	Lead	Total value
Josephine County: Galice Grants Pass Greenback  Illinois River Lower Applegate Waldo Malheur County: Mormon Basin	1	8 4 5 9 1 2	Short tons 4, 644 2 90 1	Fine ounces 1,806 1 21 29	Fine ounces 180 207 487 217 25 405 247	Fine ounces 1, 986 208 508 246 25 407 247		Pounds 600 15, 400	Pounds	\$69, 841 7, 295 17, 829 8, 630 878 16, 137 8, 672
Union County: Camp Carson	5	3	15, 315	1,660	4, 191	5, 8 <b>5</b> 1	70, 803	180, 000	46,000	279, 996
Total Oregon	48	83	31, 728	7, 897	38, 336	46, 233	87, 376	206, 000	46,000	1, 708, 297

Only those counties and districts shown separately for which Bureau of Mines is at liberty to publish figures; others producing listed in footnote 10 and their output included under "Combined counties and districts."
 Excludes itinerant prospectors, snipers, high-graders, and others who gave no evidence of legal right to property.
 Source of total silver as follows: 80,235 ounces from lode mines and 7,141 ounces from

<sup>4</sup> Included under "Combined counties and districts."
5 Exclusive of placer output, which is included under "Combined counties and districts."

<sup>Greenhorn district lies in both Baker and Grant Counties.
Mormon Basin district lies in both Baker and Malheur Counties.
Output from a property not classed as a "mine."
Greenback district lies in both Jackson and Josephine Counties.
Includes following districts: Baker (placer) in Baker County; Granite (placer) in Grant County; Elk Creek and Greenback in Jackson County; Ashwood in Jefferson County; and Bohemia in Lane County.</sup> 

のできた。これは、100mmのでは、1

#### BAKER COUNTY

Baker district.—The Midas mine in the Pocahontas section of the Baker district was worked by drifting and hydraulicking during 1942.

The Alec Johnson mine shipped gold ore to a smelter.

Cracker Creek district.—The Argonaut mine shipped gold ore to a smelter during 1942. The Bald Mountain mine was worked by lessees; 2 tons of high-grade ore treated by amalgamation yielded 7 ounces of gold and 5 ounces of silver, and 26 tons of gold ore shipped to a smelter contained 14 ounces of gold and 144 ounces of silver. The Ellis Mining Co. remodeled the E & E mill in 1942; the company holdings, which include the Eureka & Excelsior, Tabor Fraction, and Columbia mines, were operated by lessees, who shipped to a smelter 3,472 tons of ore containing 2,156 ounces of gold, 5,980 ounces of silver, and 6,196 pounds of copper.

Greenhorn district.—The Sunshine Mining Co. (Burnt River Division) operated a connected-bucket dredge in 1942 until War Production Board Order L-208 resulted in suspension of operations in October. The Oroplata Mining Co. operated a dragline dredge near Whitney from January 25 until March 11, when operations were suspended for the duration of the war; the dragline excavator was

equipped with a 2½-cubic yard bucket.

Mormon Basin district.—G. W. Cartwright hydraulicked at the Rye Valley placers during 1942. J. W. Frisco worked the Webber mine by hydraulicking from June 1 until September 30 and recovered

19 ounces of gold and 14 ounces of silver.

Sparta district.—Lessees worked the Macy mine from January 1 to February 21, 1942, when the lease was terminated; 60 tons of ore treated by amalgamation yielded bullion, containing 11 ounces of gold and 4 ounces of silver, and 1 ton of gravity concentrate, contain-

ing 2 ounces of gold and 1 ounce of silver.

Sumpter district.—The Sumpter Valley Dredging Co., largest producer of gold in Oregon in 1942, washed 2,704,734 cubic yards of gravel and recovered 10,259 ounces of gold and 2,360 ounces of silver; the dredge (Yuba type) had seventy-two 9-cubic foot buckets. Operations were suspended October 31 because of War Production Board Order L-208. Consuelo Oregon Mines operated a dragline dredge during the first 6 months, and the Northwest Development Co. operated a dragline dredge on Powder River during the first 7 months of the year.

Upper Burnt River district.—G. W. Elliott worked the Elliott drift mine from January 1 to August 1, 1942; 800 cubic yards of gravel

yielded 25 ounces of gold and 4 ounces of silver.

Virtue district.—K. Grabner operated the Cliff mine from January 1 to July 1, 1942; 100 tons of ore treated by amalgamation yielded 32 ounces of gold and 5 ounces of silver; 48 tons of gold ore shipped to a smelter contained 42 ounces of gold and 7 ounces of silver. Old tailings at the Gold Center mine were treated by cyanide leaching between June 1 and October 1.

Weatherby district.—Lovejoy Mines, in the Chicken Creek section of the Weatherby district, produced a small quantity of gold by

amalgamation in 1942.

GRANT COUNTY

Canyon district.—Hydraulicking at the Quartz Gulch mine from February 15 to July 5, 1942, resulted in the recovery of 20 ounces of

gold and 4 ounces of silver from 8,000 cubic yards of gravel. Hydraulicking was carried on at the Tracy mine from March 5 to May 5. Ferris Mining Co. operated a dragline dredge from January 1 until operations were suspended October 26; the dragline excavator was equipped with a 3-cubic yard bucket. The Western Gold Dredging Co. operated a connected-bucket dredge on John Day River from January 1 to October 13; the dredge had seventy-two 6-cubic foot buckets.

Granite district.—Porter & Co. operated a connected-bucket dredge with sixty-two 4½-cubic foot buckets on Granite, Clear, Olive, and Crane Creeks from January 1 until October 16, 1942. Bruce Dennis operated the Constitution mine; gold ore was treated by flotation, and gold concentrates were shipped to a smelter. The Cougar-Independence Mining Co. shipped gold ore and gold concentrates from the Cougar Independence mine; operations were suspended when repair

parts for the company mill became unobtainable.

Greenhorn district.—The Timms Gold Dredging Co. during 1942 operated a connected-bucket dredge on the DeWitt ranch situated in that part of the Greenhorn district extending into Grant County from Baker County. Klein & Manley amalgamated 16 tons of ore from the Golden Gate mine and recovered 30 ounces of gold and 5 ounces of silver. W. Gardner shipped gold ore from the Morning mine to a smelter. James & Hay carried on development work at the Rabbit mine from January 1 to December 1; gold ore was treated by amalgamation.

North Fork John Day district.—A gold shipment was made from the North Fork placer in 1942 as a result of the final clean-up of the

dragline dredge which had suspended operations in 1941.

#### JACKSON COUNTY

Elk Creek district.—A small quantity of lead concentrates resulted from test work carried on during 1942 by Al Sarena Mines, Inc., at the Al Sarena mine in the Buzzard section of the Elk Creek district;

the concentrates were shipped to a smelter.

Gold Hill district.—Stearns & Owens operated a dragline dredge on the Kubli ranch from January 1 until October 7, 1942; the dragline excavator was equipped with a 2-cubic yard bucket. Lance Bros. hydraulicked 1,000 cubic yards of gravel between January 1 and April 1, recovering 20 ounces of gold and 3 ounces of silver. Pleasant Creek Mining Corporation operated a connected-bucket dredge on Pleasant Creek from January 1 to June 1; the dredge was equipped with fifty-six 3-cubic foot buckets. H.H.McClung recovered 16 ounces of gold and 3 ounces of silver by hydraulicking on Wards Sandry & Whipple operated the Gold Chloride mine from January 1 to June 20; 38 ounces of gold and 9 ounces of silver were recovered from 36 tons of ore. J. T. Breeding worked the Lucky Bart group during the year.

Greenback district.—H. B. Warner shipped high-grade gold ore from intermittent operations at the Warner mine to a smelter during 1942.

Jacksonville district.—The Jackson Mining Co. operated a nonfloating washing plant, to which gravel was delivered by mechanical means, on the George Wendt ranch from January 1 until March 1, 1942. The C. & D. Mining Co. operated a dragline dredge with a dragline excavator, having a 11/2-cubic yard bucket, from January 1 to April 25;

AND DESCRIPTION OF THE PROPERTY OF THE PROPERT

A CAR STANDARD

20,000 cubic yards of gravel yielded 170 ounces of gold and 27 ounces

of silver.

Upper Applegate district.—Stearns & Owens operated a dragline dredge on the Alaska of Oregon and B-H properties during 1942. The B-H Co. operated a dragline dredge with a dragline excavator, having a 1½-cubic yard bucket, from January 1 to May 7; 177,500 cubic yards of gravel yielded 843 ounces of gold and 131 ounces of silver. F. L. Smith carried on intermittent hydraulicking on the Federal mine throughout the year. The Crescent Pacific Mining Co. operated a dragline dredge with a dragline excavator equipped with a 1¾-cubic yard bucket from January 1 to 28, and 45,850 cubic yards of gravel yielded 174 ounces of gold and 22 ounces of silver; a caterpillar and carry-all was used for resoiling the dredge area. The Southern Oregon Mining Co., Ltd., operated a dragline dredge on the McDonough and the Smith-McDonough ranches from January 1 to May 5; the dragline excavator was equipped with a 1½-cubic yard bucket. Hydraulicking was carried on at the Sterling property during the season.

#### JEFFERSON COUNTY

Ashwood district.—Oregon King Mines, Inc., operated the Oregon King mine from January until October 1942, when work was continued by Fenton & Silbaugh under the name of Oregon King Mines; 1,180 tons of gold-silver ore and 400 tons of old tailings were treated in the company 50-ton flotation mill; 261 tons of resulting gold-silver concentrates and 1,035 tons of silver ore were shipped to a smelter. The concentrates contained 131 ounces of gold, 17,338 ounces of silver, 5,815 pounds of copper, 14,185 pounds of lead, and 18,103 pounds of zinc; the ore shipped direct to the smelter contained 202 ounces of gold, 39,459 ounces of silver, 9,742 pounds of copper, 17,566 pounds of lead, and 37,351 pounds of zinc.

#### JOSEPHINE COUNTY 1

Galice district.—S. Alderson carried on hydraulicking operations at the Klum mine from February 2 to April 13, 1942. Young & Vandeventer hydraulicked at the Lewis mine. The Lewis Investment Co. operated the Benton mine from January 1 to April 8, when work was suspended because of rising costs of supplies and shortage of labor; gold ore was treated in the company 60-ton countercurrent cyanidation plant. Gold ore was shipped from the Almeda mine.

Grants Pass district.—R. Heller operated the Sunset mine on Jumpoff Joe Creek during 1942; 4,000 cubic yards of gravel yielded 17 ounces of gold and 2 ounces of silver. The Yewwood mine was also

worked by hydraulicking.

Greenback district.—Hydraulicking was carried on at the Blue Channel mine from January 1 to May 1, 1942. The Little Artie mine was worked. Gold was produced by hydraulicking at the Goff mine during the year.

Illinois River district.—Laguna Mines hydraulicked during 1942. N. W. Cole worked the Eureka mine from January 1 to August 1.

Waldo district.—Hydraulicking at the Esterly mine in 1942 yielded 373 ounces of gold and 21 ounces of silver from the washing of 63,700

<sup>1</sup> See also State of Oregon Department of Geology and Mineral Industries, Oregon Metal Mines Handbook: Bull. 14-C, 1942, 229 pp.

cubic yards of gravel. A small shipment of copper ore from the Cow Boy mine was sent to a smelter.

#### LANE COUNTY

Bohemia district.—H. & H. Mines completed construction of a mill and power plant at the Champion mine in 1942; gold ore was treated in a 100-ton flotation plant, and copper and lead concentrates were shipped to a smelter. High cost of materials and shortage of labor caused suspension of operations in August.

#### MALHEUR COUNTY

Mormon Basin district.—Whitney & Boydstun operated a non-floating washing plant, to which gravel was delivered by a carry-all, from March 10 to July 10, 1942; 16,000 cubic yards of gravel yielded 240 ounces of gold and 38 ounces of silver.

#### OTHER COUNTIES

Small outputs in 1942 were reported from Coos, Curry, Douglas, Harney, and Union Counties.

Details of production by counties and districts are given in the preceding table.

## GOLD, SILVER, COPPER, LEAD, AND ZINC IN SOUTH DAKOTA

(MINE REPORT)

By Chas. W. HENDERSON

#### SUMMARY OUTLINE

	Page		Page
Summary		Mining and metallurgic industry	473
Calculation of value of metal production	471	Metallurgic recovery	473
Mine production by counties	473	Review by counties	474

#### SUMMARY

Metal mining in South Dakota is confined to a small area comprising parts of Custer, Lawrence, and Pennington Counties in the mountain group known as the Black Hills. Gold is the chief metal produced, and gold mining is the principal mineral industry of the State. Such minor minerals as columbo-tantalite, tin, beryllium, and lithium minerals have been produced. An extensive deposit of manganese-bearing shales near Chamberlain, Brule County, was mined experi-mentally by the International Minerals & Chemical Corporation under a War Production Board contract. Development of this project was halted early in 1943 by the War Production Board because the expenditure of manpower and equipment was not deemed advisable at that time. The Federal Bureau of Mines for a number of years has been developing the metallurgy of this deposit so that economic beneficiation may be made possible. In 1942 the recovered output of gold in the State was 522,098 fine ounces valued at \$18,273,430, a 13-percent decrease from 1941. Factors contributing to the decline in gold production were: The difficulty that gold-mine operators experienced in securing adequate labor and essential supplies and the issuance of the War Production Board Gold-Mining Limitation Order in October 1942. By September 10 all but three gold mines had closed, and the order compelled another mine to close on November 26, leaving but two in operation and those only because of a reprieve. Besides gold, South Dakota in 1942 produced 186,937 fine ounces of recovered silver valued at \$132,933 and 2,000 pounds of recovered copper as byproduct metals. In addition, 230,000 pounds of recovered zinc and 170,000 pounds of recovered lead were produced; this output came from a well-known zinc-lead deposit unprofitable to mine were it not for the premium prices for these metals.

All tonnage figures are short tons and "dry weight"; that is, they

do not include moisture.

The value of the metal production herein reported has been calculated at the following prices.

### Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zinc 4
1938	Per fine ounce \$35.00 35.00 35.00 35.00 35.00	Per fine ounce 5 \$0.646+ 6.678+ 7.711+ 7.711+ 7.711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057 .067	Per pound \$0.048 .052 .063 .075

¹ Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.
² Treasury buying price for newly mined silver.
² 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.
⁴ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.

5 \$0.64646464.

6 \$0.67878787.

7 \$0. 71111111.




FIGURE 1.—Total value of mine production of gold and silver in South Dakota, 1876-1942.

## Mine production of gold, silver, copper, lead, and zinc in South Dakota, 1938-42, and total, 1876-1942, in terms of recovered metals 1

Year	Minesproducing		Ore (short	Gold (lode and placer) Silver (lode and			and placer)
	Lode	Placer	tons)	Fine ounces	Value	Fine ounces	Value
1938 1939 1940 1941 1942	11 18 11 10 5	71 80 81 41 13	1, 586, 181 1, 632, 778 1, 667, 370 1, 711, 744 1, 464, 384	594, 847 618, 536 586, 662 600, 637 522, 098	\$20, 819, 645 21, 648, 760 20, 533, 170 21, 022, 295 18, 273, 430	162, 295 167, 584 175, 514 170, 771 186, 937	\$104, 918 113, 754 124, 810 121, 437 132, 933
1876-1942			(2)	20, 560, 041	501, 198, 644	9, 533, 213	6, 781, 561

Year	Copper		Le	ead	Zi		
Tear	Pounds	Value	Pounds	Value	Pounds	Value	Total value
1938 1939							\$20, 924, 563
1940 1941	12,000	\$1,356	14,000	\$700			21, 762, 514 20, 660, 036
1942	2,000	242	170,000	11, 390	230,000	\$21, 390	21, 143, 732 18, 439, 385
1876-1942	³ 105	36, 196	³ 380	46, 910	3 115	21, 390	508, 084, 701

<sup>&</sup>lt;sup>1</sup> For total production of gold and silver in South Dakota, by years, see Mineral Resources, 1913, pt. 1, p. 42; Mineral Resources, 1922, pt. 1, p. 194; and subsequent volumes of Mineral Resources and Minerals Yearbook.

<sup>2</sup> Figures not available.

3 Short tons.

Gold and silver produced at placer mines in South Dakota, 1938-42, in terms of recovered metals

	Gu	old	Silve	<b>7</b> 7-4-11	
Year	Fine ounces	Value	Fine ounces	Value	Total value
1938 1939 1940 1941 1942	1, 069 622 229 93 33	\$37, 415 21, 770 8, 015 3, 255 1, 155	82 47 21 7 3	\$53 32 15 5	\$37, 468 21, 802 8, 030 3, 260 1, 157

#### MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in South Dakota in 1942, by counties, in terms of recovered metals

			,	,,	0,			
County		Mines pro- ducing		Ore sold or treated	Gold (lode	and placer)	Silver (lode and placer)	
		Lode	Placer	(short tons)	Fine ounces	Value	Fine ounces	Value
Lawrence Pennington		4	10 3	1, 446, 770 17, 614	520, 006 2, 092	\$18, 200, 210 73, 220	186, 480 457	\$132, 608 325
Total, 1941		5 10	13 41	1, 464, 384 1, 711, 744	522, 098 600, 637	18, 273, 430 21, 022, 295	186, 937 170, 771	132, 933 121, 437
		Copp	er		Lead	Zin	c	/D-4-1l
County	Pot	ınds	Value	Pounds	Value	Pounds	Value	Total value
Lawrence Pennington		2,000	\$24	2 170,00	\$11,390	230, 000	\$21, 390	\$18, 365, 840 73, 545
Total, 1941		2,000	24	2 170, 00	0 11,390	230,000	21, 390	18, 439, 385 21, 143, 732

### MINING AND METALLURGIC INDUSTRY

Producers of lode gold and silver in South Dakota in 1942 mined and sold or treated 1,464,384 short tons of ore yielding, in recovered metals, 522,065 fine ounces of gold, 186,934 fine ounces of silver, 2,000 pounds of copper, 170,000 pounds of lead, and 230,000 pounds of zinc. An analysis of methods of treatment shows 1,275,138 tons treated by amalgamation followed by cyanidation of sands and slimes; 179,249 tons treated by cyanidation only or by roasting followed by cyanidation; 17,614 tons (included in 179,249 tons above) treated by table and jig concentration (some of the gold concentrates were shipped to smelter and some cyanided by countercurrent-decantation cyanidation); and 9,997 tons treated by flotation concentration.

#### METALLURGIC RECOVERY

Gold and silver bullion produced at mills in South Dakota by amalgamation, 1938-42

Year	Ore treated	Gold in bullion	Silver in bullion	Quicksilver used	
1938	Short tons	Fine ounces	Fine ownces	Pounds	
	1, 430, 391	328, 044, 50	62, 602	7, 744	
	1, 461, 283	336, 424, 93	64, 710	9, 221	
	1, 479, 905	313, 964, 15	60, 254	4, 997	
	1, 506, 183	328, 166, 44	62, 423	6, 537	
	1, 275, 138	276, 298, 00	56, 852	3, 561	

Gold and silver bullion produced at mills in South Dakota by cyanidation, 1938-42

		Mater	ial treated	Gold in	Silver in	Sodium	
Year	Crude ore	Concen- trates	Sands and slimes	Total	bullion product	bullion product	cyanide used <sup>1</sup>
1938	Short tons 155, 667 170, 270 187, 360 205, 356 161, 635	Short tons 2 61 3 366	Short tons 1, 416, 899 1, 443, 548 1, 432, 244 1, 499, 000 1, 271, 305	Short tons 1, 572, 566 1, 613, 879 1, 619, 604 1, 704, 356 1, 433, 306	Fine ounces 262, 913. 21 279, 889. 77 269, 518. 82 270, 989. 89 244, 421. 00	Fine ounces 98, 777 102, 317 111, 607 106, 437 122, 312	Pounds 860, 762 887, 888 883, 849 903, 680 4 801, 478

In terms of 96- to 98-percent strength.
 From 1,143 tons of ore treated by flotation.
 From 1,7614 tons of crude ore treated by table and jig concentration.
 Actually 1,602,955 pounds of calcium cyanide (48- to 49-percent strength); all reduced to equivalent of 96- to 98-percent strength to conform with earlier use of figures for high-strength NaCN and KCN.

#### REVIEW BY COUNTIES

#### CUSTER COUNTY

There were no mining operations in Custer County in 1942 other than a small amount of development work on several placer properties The inactivity in this district is due largely to along French Creek. the fact that relatively little virgin placer ground remains, and most of the residents who formerly mined have taken more lucrative jobs in war industries.

#### LAWRENCE COUNTY

Homestake mine.—The Homestake mine has been producing almost continuously since 1876 and has been operated since 1877 by the Homestake Mining Co. This company at first owned only the Homestake and Golden Star claims but has since acquired and consolidated into one group numerous other claims which, with the first two, constitute the Homestake mine. The annual report of the general manager of the Homestake Mining Co. for the year ended December 31, 1942, savs-

Operations during 1942 were seriously affected by war conditions and by orders of the War Production Board. Difficulties began in March, when priority ratings for gold mines were lowered and culminated with the drastic order issued October 8, 1942, suspending operations of gold mines. An appeal from this order was filed with the War Production Board and modification obtained to permit hoisting and milling of broken ore for an additional period of 6 months or until June 8, 1943.

Ore production from the mine during 1942 was 1,275,138 tons which is a decrease of 14.99 percent from that for 1941. The gross income for gold and silver produced was 12.63 percent lower than in 1941. The average realization per ton was \$13.39 as compared to \$13.02 in 1941.

Total taxes were \$4,269,162.87, which is \$108,828.26 more than in 1941. The reserve of developed ore is 19,183,683 tons, which includes 270,092 tons of

broken ore remaining in the shrinkage stopes.

The mine and plant are in excellent condition and, unless circumstances arise beyond our control, this condition will be maintained in order that production can be resumed when present Government restrictions are withdrawn.

All construction was completed early in the year. The new mine and engineering office was completed and occupied in May. The Yates shaft was sunk to a depth of 145 feet below the 4,100-foot level and a skip loading station excavated below that level.

Machine shops and foundry are engaged in a variety of war production jobs. The sawmill at Spearfish is continuing to operate at capacity. Its production of lumber is being sold largely for army bases and other construction for military purposes.

Early in the year investigation of properties that might yield metals necessary to the war effort was begun. In July an option was taken on a manganese property in Lower California. Plans for a mill are under consideration. In October, the development and operation of a deposit in Wyoming containing a strategic mineral was undertaken through an agency contract made by your subsidiary, the Wyodak Coal & Mfg. Co., with the Metals Reserve Co. Performance is guaranteed by the Homestake Mining Co. Only nominal profits at best may be expected from these operations undertaken as part of the war effort.

With the order of the War Production Board as it now stands it is expected that production from ore previously broken will continue at approximately 1,000 tons per day for the first 5 months of 1943. Expenses during the period of curtailed production and subsequent period without any production will be reduced

to the minimum consistent with proper maintenance of the properties.

As a result of war conditions and the order of the War Production Board, the total number of our employees has been reduced from 2,200 to 800. This has brought distress to many and great damage to our communities. It has been with deep regret that we have been forced to release a large number of employees with long and faithful service with our company. \* \* \* 385 former members of our staff are now with the armed forces.

Ore milled, receipts, and dividends, Homestake mine, 1938-42 1

			Ore milled	Receipts for bull	ion product	Dividends
aturi (e.) Kulon (e.)	Year		short tons)	Total	Per ton	Dividends
1938	 	 	 1, 377, 314 1, 400, 015	\$19, 284, 459. 67 19, 922, 964. 60	\$14.0015 14.2300	\$9, 041, 760 9, 041, 760
1939 1940 1941	 	 	 1, 433, 737 1, 499, 988	19, 014, 767. 73 19, 529, 080. 70	13. 2624 13. 0195	9, 041, 760 9, 041, 760
1942	 	 	 1, 275, 138	17, 068, 437. 84	13, 3856	7, 534, 800

<sup>1</sup> From 1876 to 1942, inclusive, this mine yielded bullion and concentrates that brought a net return of \$435,610,266 and paid \$149,805,802 in dividends.

Other mines.—The Bald Mountain Mining Co., second-largest producer of gold and silver in South Dakota in 1942, operated continuously throughout the year its consolidated group of mines and 370-ton cyanide mill at Trojan at an average rate of 302 tons of ore daily. Ore was produced in 1942 from the Portland, Two Johns, Dakota, Trojan, Clinton, and Empire claims. Development work done on these claims in 1942 totaled 1,932 feet of drifts and 325 feet of raises. The mill treated 131,152 tons of dry gold ore, from which 22,787 fine ounces of gold and 66,184 fine ounces of silver were recovered. About 16 percent of the ore produced was sulfide (locally known as "blue ore"), and 75 percent was oxide (locally known as "brown ore"). Following primary crushing, the refractory sulfide ores not amenable to treatment by straight cyanidation are roasted in the 110-ton gasfired rotary hearth furnace and then returned to the mill circuit and mixed with the oxide ores for cyanidation. The net return from metals produced in 1942 after transportation and mint and smelter charges were deducted was \$842,320.

At the Maitland group of claims 5½ miles northwest of Deadwood the Canyon Corporation continued operations of its 120-ton roast-cyanide mill until November 26, 1942, when the corporation closed the mine, removed the pumps, and dismantled surface buildings. Total dry gold ore treated in the mill was 30,483 tons from which 10,295 fine ounces of gold and 1,668 fine ounces of silver were recovered. Besides gold and silver, the ores contain pyrite, marcasite, fluorite, and traces of arsenic. The mine is opened by a vertical shaft 600 feet

deep and by drifts and winzes.

The Belle Eldridge Gold Mines, Inc., began production of zinc-lead ore, milled on the property to make zinc and lead concentrates, from its group of claims in the Whitewood district March 12, 1942, and continued operations throughout the remainder of the year. The new 75-ton selective-flotation mill completed in March 1942 converted 9,997 tons of crude ore into 216 tons of lead concentrates and 290 tons of zinc concentrates which, combined, contained 174 fine ounces of gold, 7,946 fine ounces of silver, 2,842 pounds of copper, 193,286 pounds of lead, and 259,196 pounds of zinc. Development work in 1942 consisted of 1,020 feet of drifts, 500 feet of tunnel, and 500 feet of diamond drilling. Production came solely from the Helen Gould claim.

Placer activity in Lawrence County in 1942 was very small. The Driskill Co. handled about 2,800 cubic yards of gravel on the Little Tom placers on Potato Creek 2 miles east of Tinton with a %-cubic yard power shovel and land dredge and recovered 14.5 fine ounces of gold and 1 fine ounce of silver. Other placer activity, chiefly on Bear Butte Creek in the Bear Butte district and Whitewood Creek in the Whitewood district, consisted of nine small hand-sluicing and panning operations which produced a total of only 13.5 fine ounces

of gold and 2 fine ounces of silver.

#### PENNINGTON COUNTY

The Holy Terror Mining Co. operated its Holy Terror-Keystone mine and 100-ton cyanide mill in the Keystone district continuously until September 10, 1942, treating 17,614 tons of dry gold ore. A jig and table in the ball-mill circuit produced concentrates, part of which were shipped to the Helena (Mont.) smelter of the American Smelting & Refining Co. Most of the concentrates produced were treated in the countercurrent-decantation cyanidation circuit of the mill. Development work completed in 1942 consisted of unwatering 200 feet of shaft and driving 960 feet of drift.

Only three small hand-sluicing or panning placer operations were conducted in Pennington County in 1942—the Gold Run in the Hill City district and the Rockerville and Golden Rule in the Rapid Creek district. These placers yielded a total of only 5 fine ounces

of gold.

## GOLD, SILVER, COPPER, LEAD, AND ZINC IN TEXAS

(MINE REPORT)

By Chas. W. HENDERSON

#### SUMMARY OUTLINE

Pa	age	r en la servició de la filología de la composició de la composició de la composició de la composició de la comp	Page
Summary	477	Smelting and refining plants in Texas	 479
Calculation of value of metal production			 _ 479
Mine production	478		
Ore classification	478 l		True of

#### SUMMARY

Texas mines produced gold, silver, copper, and lead in 1942 valued at \$534,894, in terms of recovered metals; this value, compared with \$812,727 in 1941, represents a decline of 34 percent, due largely to the 39-percent slump in silver output. Gold declined slightly, and lead remained virtually at the 1941 figure; but copper increased more than 1500 percent in quantity. No zinc has been recovered from ores

mined in Texas since 1917.

Silver, the principal metal produced in Texas, was first found in 1880 at the Presidio mine at Shafter, Presidio County, but shipments of bullion were not begun until 1885. From that date until September 1942 this mine was by far the outstanding producer of the Statechiefly of silver but also of gold and lead. Other mines producing more than 1,000 ounces of silver in 1942 were the Bird mine in Brewster County, the Hazel mine in Culberson County, and the Sancho Panza mine in Hudspeth County. The American Metal Co. of Texas operated the Presidio mine and 400-ton cyanidation mill at Shafter continuously until September 6, 1942, when the company ceased operations. About 3,500 tons of silver smelting ore, carrying some copper, were shipped from the Sancho Panza mine near Allamoore to the El Paso smelter. About 470 tons of copper ore from the Hazel mine, 23 tons of silver ore from the Needle Peak mine, and 139 tons of lead ore (containing silver) from the Bird mine were shipped to the El Paso smelter.

#### Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zine 4
1938 1939 1940 1941	Per fine ounce \$35.00 35.00 35.00 35.00	Per fine ounce \$ \$0.646+ 6.678+ 7.711+ 7.711+	Per pound \$0.098 .104 .113 .118	Per pound \$0.046 .047 .050 .057	Per pound \$0.048 .052 .063 .075

<sup>1</sup> Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.

2 Treasury buying price for newly mined silver.

2 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.

4 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.

4 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.

4 30. 64846464.

All tonnage figures are short tons and "dry weight"; that is, they do not include moisture.

The value of the metal production herein reported has been calculated at the prices in the preceding table.

#### MINE PRODUCTION

The following table shows the annual output of ore and the quantity and value of the metals recovered from Texas mines from 1938 to 1942, as well as the total metal production from 1885 to 1942.

Mine production of gold, silver, copper, lead, and zinc in Texas, 1938-42, and total, 1885-1942, in terms of recovered metals

	Ore (short	G	old	Silver		
Year	tons)	Fine ounces	Value	Fine ounces	Value	
1938	131, 002 141, 795 146, 936 140, 818 100, 698	439 324 312 306 236	\$15, 365 11, 340 10, 920 10, 710 8, 260	1, 433, 008 1, 341, 945 1, 326, 150 1, 096, 027 672, 781	\$926, 389 910, 896 943, 040 779, 397 478, 422	
1885-1942	(1)	8, 277	223, 640	33, 186, 537	23, 352, 715	

Year	Copper		Lead		Zine		(Data)
1 cai	Pounds	Value	Pounds	Value	Pounds	Value	Total value
1938	32, 000 68, 000 60, 000 12, 000 198, 000	\$3, 136 7, 072 6, 780 1, 416 23, 958	684, 000 454, 000 410, 000 372, 000 362, 000	\$31, 464 21, 338 20, 500 21, 204 24, 254			\$976, 354 950, 646 981, 240 812, 727 534, 894
1885-1942	² 1, 055	302, 111	<sup>2</sup> 4, 775	487, 499	2 744	\$106, 491	24, 472, 456

<sup>&</sup>lt;sup>1</sup> Figures not available.

Mine production of gold, silver, copper, and lead in Texas in 1942, by counties, in terms of recovered metals

County	Mines pro- ducing	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)
Brewster	1 2 2 2 2	139 492 3, 549 96, 518	1 235	3, 230 2, 496 2, 343 664, 712	200 28, 000 166, 600 3, 200	69, 000 1, 000 292, 000
Total, 1941	7 9	100, 698 140, 818	236 306	672, 781 1, 096, 027	198, 000 12, 000	362, 000 372, 000

#### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

Ore sold or treated in Texas in 1942, with content in terms of recovered metals

Source	Mines pro-	Ore (short	Gold (fine	Silver (fine	Copper	Lead
	ducing	tons)	ounces)	ounces)	(pounds)	(pounds)
Dry and siliceous silver ore Copper ore Lead ore	3 2 2	100, 052 506 140	235 1	667, 454 2, 089 3, 238	167, 562 30, 238 200	292, 000 70, 009
Total, 1941	7	100, 698	236	672, 781	198, 000	362, 000
	9	140, 818	306	1, 096, 027	12, 000	372, 000

Short tons.

## SMELTING AND REFINING PLANTS IN TEXAS

In 1942 two zinc retort smelters (one of which has a cadmium-recovery plant), one copper smelter, one lead smelter, one antimony smelter, one tin smelter, one electrolytic plant for extraction of magnesium from sea water, and one electrolytic copper refinery were operating in Texas; a new electrolytic zinc smelter was completed and

set in operation.

The American Smelting & Refining Co. continued to operate its copper and lead smelters at El Paso in 1942, treating ores purchased from operators in Arizona, New Mexico, Texas, and Utah and in Mexico. Ores from Canada, South America, Africa, and many other foreign sources continued to be received (as in 1941) at El Paso after their original destinations had fallen into enemy hands. The El Paso plant contains a unit for recovering arsenic in addition to the lead and copper furnaces.

The American Smelting & Refining Co. gas-retort zinc smelter at Amarillo was operated virtually at capacity throughout the year, treating zinc concentrates purchased from operators in Arizona, Colorado, Idaho, Montana, Nevada, New Mexico, and South Dakota and in Mexico. The electrolytic zinc plant recently completed by the company at Corpus Christi, designed to operate on zinc concentrates from Buchans, Newfoundland, was opened on stored Buchans

concentrates and Mexican concentrates.

The Machovec gas-retort zinc smelter of the American Zinc, Lead & Smelting Co. at Dumas, purchased from the Illinois Zinc Co., was operated at maximum capacity throughout the year on zinc concentrates from operators in New Mexico, Utah, Mexico, and Newfoundland. Operation of the cadmium plant was entirely satisfactory, and production of cadmium will be substantially increased during the second quarter of 1943. According to the contract with the Defense Plant Corporation, as of July 1942, the American Zinc, Lead & Smelting Co. installed additional slab zinc-producing facilities at the Dumas plant, some of which were in production before the end of 1942.

The Nichols electrolytic copper refinery at El Paso, a unit of the Phelps Dodge Corporation, continued to refine copper anodes produced at corporation smelters in Arizona. The plant was operated at

capacity throughout the year.

### MINES REVIEW BY COUNTIES

Brewster County.—The Bird mine 5 miles northwest of Altuda was operated throughout 1942 by the Bird Mining Co., Inc., and regular shipments began on March 10, 1942, to the smelter at El Paso. Lead ore totaling 139 tons, containing 3,230 ounces of silver, 296 pounds of copper, and 77,107 pounds of lead, was shipped during 1942. Development work in 1942 comprised 700 feet of drifts and 64 feet of winze.

Culberson County.—Copper ore totaling 469 tons, containing 2,081 ounces of silver and 28,242 pounds of copper, was shipped from the Hazel mine 14 miles northwest of Van Horn to the El Paso smelter. The mine was operated by J. P. Witherspoon, lessee, with A. P. Williams as mine superintendent; it is opened by a vertical shaft 320 feet deep. A small lot (23 tons) of dry silver ore containing 415 ounces of silver and 1,002 pounds of copper was shipped from the Needle Peak open-cut near Van Horn to the El Paso smelter.

Hudspeth County.—Lessees on the Sancho Panza mine 7 miles northeast of Allamoore shipped 3,548 tons of silver smelting ore containing 2,335 ounces of silver and 172,801 pounds of copper to the smelter at El Paso. One ton of lead ore containing 1,139 pounds of lead was shipped from Sierra Blanca to the El Paso smelter by the Lancaster Lead Co.

Presidio County.—Two small lots—34 tons and 3 tons of copper ore containing 3,206 and 332 pounds of copper, respectively—were shipped

from Shafter to the smelter at El Paso.

The American Metal Co. of Texas operated its Presidio mine at Shafter continuously until September 6, 1942, when the company ceased all operations; shortly afterward all the equipment of the property was dismantled and shipped. Labor difficulties, excessive water in the lower levels, lowering of the grade of ore, and depletion of ore reserves were contributory factors to closing of the property. The quantity of ore treated was 96,481 tons compared with 140,503 tons in 1941. Development work in 1942 comprised 2,124 feet of drifts and 12,421 feet of diamond drilling. The ore minerals are argentite, anglesite, cerussite, cerargyrite, and galena. In 1942 the mill produced 545,360 ounces of silver and 213 ounces of gold in cyanide precipitates, and 396 tons of table concentrates containing 22 ounces of gold, 119,344 ounces of silver, and 283,628 pounds of lead. The cyanide precipitates carried 14,852 pounds of lead dissolved by the cyanide. The concentrates and precipitates were shipped to the Carteret (N. J.) smelter.

Production of silver from the Presidio mine, 1 1885-1942 2

Period	Mill heads Silver content of mill heads (ounces)		Recovery of silver		
	(short tons)	Per ton	Total	Percent	Ounces
1885-1912 1913-26 1927 1928 1929 Total, 1885-1929	48, 190 57, 475 54, 644 1, 330, 309 24, 985	25. 84 12. 00 22. 87 23. 17 19. 74 17. 88 16. 09	11, 628, 000 8, 640, 000 1, 102, 105 1, 331, 696 1, 078, 673 23, 780, 474 401, 926	81. 68 83. 66 91. 41 91. 04 90. 30 83. 77 88. 79	9, 497, 756 7, 228, 22: 1, 007, 43: 1, 212, 34( 974, 04: 19, 919, 797 356, 854
934 935 936 937 938 939 940 941	46, 653 70, 166 98, 499 110, 220 127, 574 138, 934 144, 558 140, 503 96, 481	19. 70 15. 87 14. 41 12. 76 12. 76 11. 24 10. 55 9. 39 8. 36	919, 064 1, 113, 686 1, 419, 371 1, 406, 825 1, 627, 844 1, 561, 618 1, 525, 087 1, 319, 323 806, 581	91. 39 87. 84 87. 48 86. 79 84. 72 83. 49 84. 90 82. 90 82. 41	839, 93 978, 30; 1, 241, 60; 1, 220, 92; 1, 379, 18; 1, 294, 80; 1, 093, 74; 664, 704
Total, 1885-1942	2, 328, 882	15.41	35, 881, 799	84. 43	30, 293, 60

<sup>&</sup>lt;sup>1</sup> Howbert, Van Dyne, and Gray, F. E., Milling Methods and Costs at Presidio Mine of the American Metal Co. of Texas: Am. Inst. Min. and Met. Eng. Tech. Pub. 368, 1930, 20 pp. Howbert, Van Dyne, and Bosustow, Richard, Mining Methods and Costs at Presidio Mine of the American Metal Co. of Texas: Am. Inst. Min. and Met. Eng. Tech. Pub. 334, 1930, 15 pp. Stem, D. E., Milling Methods and Costs at the Presidio Mine: Arizona Min. Jour., vol. 24, No. 22, April 15, 1941, pp. 3–5.

## GOLD, SILVER, COPPER, LEAD, AND ZINC IN UTAH

#### (MINE REPORT)

By G. E. WOODWARD AND PAUL LUFF

#### SUMMARY OUTLINE

	Page		Page
Summary	481	Metallurgic industry	487
Calculation of value of metal production	482	Review by counties and districts	491
Mine production by counties	485		
Mining industry			
Ore classification	486	Park City region	498

#### SUMMARY

Ores and gravels from Utah mines yielded gold, silver, copper, lead, and zinc valued, in terms of recoverable metal, at \$113,552,848 in 1942 compared with \$97,796,623 in 1941. The increase in output of recoverable copper accounted for most of the gain, although increases were noted in output of all metals except silver. The total gain in value of the State metal output can be credited largely to the Bingham district, although the Park City region showed a gain in gold production and the Tintic district in lead and zinc production. The Utah Copper Co. in 1942 surpassed by far its outstanding production record established in 1941 and contributed over 70 percent of the value of the total metal output of the State. The output of zinc from Tooele County increased in 1942, whereas the output of each of the other metals decreased.

The production of copper, and more particularly that of lead and zinc, in 1942 was affected by several factors. The Metals Reserve Company announced that, effective February 1, 1942, premiums of 5 cents a pound for copper and 2% cents a pound for both lead and zinc would be paid for these metals produced in excess of certain fixed basic quotas. Each mine or company had its basic quota fixed according to the previous year's production or through direct negotiation with the Government agency. Most mines in Utah, which were granted basic quotas under the original principle of premium payments, have since received downward adjustment favorable to the company. broaden the scope of the premium payments for over-quota metal further, the Metals Reserve Company announced that, effective December 1, 1942, at the opening of business it would allow an additional premium for lead and two additional premiums for zinc. Eligibility for these additional premiums was based primarily on the ability of the producer to maintain the present rate of output or to insure additional output. Each case was to be considered independently by the Quota Committee, Premium Price Plan for Copper, Lead, and Zinc (War Production Board—OPA).

Although the Government stimulated the production of copper, lead, and zinc by price manipulation, the full effect of the program was not realized because of the critical shortage of suitable mine, mill, and smelter labor. The labor supply became critically low during July, August, September, and part of October. In October the Army fur-

loughed 4,000 soldiers for service in mines. Of this number, Utah mines and smelters received approximately 700. This action tended to relieve the severity of the shortage but did not insure adequate labor for operations consistent with the present demand for metals. Thus, the majority of Utah mines at the close of 1942 faced the problem of either securing additional labor or endeavoring to maintain the present personnel at levels sufficient to meet production demands.

All tonnage figures are short tons and "dry weight"; that is, they

do not include moisture.

The value of the metal production herein reported has been calculated at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zine 4
1938. 1939. 1940. 1941.	Per fine ounce \$35.00 35.00 35.00 35.00 35.00	Per fine ounce \$ 0.646+ 6.678+ 7.711+ 7.711+ 7.711+	\$0.098	Per pound \$0.046 .047 .050 .057 .067	Per pound \$0.048 .052 .063 .075

¹ Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.
² ¹ Treasury buying price for newly mined silver.
² 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Company for over-quota production but excludes value of foreign copper delivered to Metals Reserve Company for domestic consumption.
² 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Company for over-quota production.
² \$0.64646464.

Mine production of gold, silver, copper, lead, and zinc in Utah, 1938-42, and total, 1864-1942, in terms of recovered metals

<b>W</b>	Mines producing		Ore (short	Gold (lode a	and placer)	Silver (lode and placer)		
Year	Lode	Placer	tons)	Fine ounces	Value	Fine ounces	Value	
1938	183 175 191 167 123	22 11 21 12 6	13, 248, 660 21, 094, 097 27, 939, 346 31, 952, 817 34, 981, 655	200, 630 277, 751 355, 494 356, 501 391, 544	\$7, 022, 050 9, 721, 285 12, 442, 290 12, 477, 535 13, 704, 040	9, 682, 732 10, 758, 657 12, 172, 299 11, 395, 485 10, 574, 955	\$6, 259, 544 7, 302, 846 8, 655, 857 8, 103, 456 7, 519, 968	
1864-1942			(1)	9, 449, 773	230, 967, 095	691, 875, 106	504, 275, 236	

Copper		pper	Le	ad	Zi		
Year	Pounds	• Value	Pounds	Value	Pounds	Value	Total value
1938 1939 1940 1941 1942	216, 252, 000 343, 780, 000 463, 728, 000 533, 676, 000 613, 382, 000	\$21, 192, 696 35, 753, 120 52, 401, 264 62, 973, 768 74, 219, 222	131, 314, 000 135, 268, 000 151, 376, 000 139, 202, 000 143, 860, 000	\$6,040,444 6,357,596 7,568,800 7,934,514 9,638,620	67, 316, 000 69, 052, 000 87, 576, 000 84, 098, 000 91, 086, 000	\$3, 231, 168 3, 590, 704 5, 517, 288 6, 307, 350 8, 470, 998	\$43, 745, 902 62, 725, 551 86, 585, 499 97, 796, 623 113, 552, 848
1864-1942_	2 3, 953, 217	1, 113, 708, 563	2 4, 229, 736	457, 350, 462	<sup>2</sup> 835, 199	104, 313, 625	2, 410, 614, 981

1 1864-1901: Figures not available; 1902-42: 456,347,638 tons produced.

Gold.—Utah mines in 1942 produced 391,544 ounces of recoverable gold—the greatest output in any year in the history of the State. By far the largest portion of Utah gold is recovered as a byproduct of the recovery of base metals; as a consequence, the gold order issued by the Government in October 1942 did not affect the State output greatly. Most mines producing siliceous ores were allowed to continue operation, so that an adequate supply of fluxing material might be available to smelters in the Salt Lake Valley. Copper

ore yielded 75 percent of the total gold and siliceous ore 10 percent; the remainder came from zinc-lead ore and slag, lead ore, lead-copper ore, zinc ore, zinc-lead-copper ore, and placers. The placer output of fine gold in 1942 was only 32 ounces. Ores of all classes treated in concentrating mills yielded 86 percent of the State total, ores shipped direct to smelters 12 percent, and ores treated by amalgamation and cyanidation, placers, and slag fumed 2 percent. Ore of the West Mountain (Bingham) district was by far the most important source of gold and in 1942 yielded 327,258 ounces (nearly 85 percent of the State total), a gain of 52,139 ounces over 1941. Gold produced from the Tintic district was slightly less than in 1941, owing to the smaller output of siliceous ores. The recoverable gold pro-




FIGURE 1.—Value of mine production of gold, silver, copper, lead, and zinc and total value in Utah, 1870-1942,

duction from the Park City region increased 3,188 ounces, owing to increases at the New Park Mining Co. Gold output from Tooele County decreased 18,523 ounces. The Utah Copper Co. produced 73 percent of the State output of gold and was followed by the United States & Lark, Mayflower, Tintic Bullion, Snyder Mines, Inc. (at Mercur), Sacramento, Mammoth, and Boston Consolidated mines; these eight properties produced 91 percent of the total gold output of Utah.

Silver.—The output of recoverable silver in Utah in 1942 was 10,574,955 ounces, of which 82 percent was derived from base-metal ore. Zinc-lead, zinc-lead-copper, and zinc ore yielded 49 percent of the State total, copper ore 26 percent, siliceous ore 18 percent, and lead and lead-copper ores 7 percent. Ore concentrated yielded 74

percent of the total and ore shipped crude to smelters virtually all the remainder. The Bingham district—chief source of silver in Utah—was followed by the Park City region, Tintic district, and Tooele County. The Utah Copper Co. was again the chief silver producer in the State; it was followed by the United States & Lark, Tintic Standard, Silver King Coalition, Park City Consolidated properties, Mayflower, Park Utah Consolidated group of properties, and Calumet; and these eight properties produced 82 percent of the silver output of Utah in 1942.

Copper.—Production of recoverable copper in Utah in 1942 was 613,382,000 pounds and completely eclipsed the former record of 533,676,000 pounds in 1941. The Utah Copper Co., by far the largest copper producer in the United States, mined about 75,000,000 tons of ore and waste from its open-pit mine at Bingham at the ratio of 1½ tons of waste to 1 ton of ore. The company mills at Arthur and Magna, although rated at a daily capacity of 78,000 tons, treated an average of over 91,000 tons a day and continued to show very high recoveries. Copper ore mined in Utah amounted to 33,611,061 tons in 1942 compared with 30,444,402 tons in 1941. Copper ore and mine-water precipitates yielded virtually the entire State output of copper. Following the Utah Copper Co., copper producers in Utah in 1942 included the Ohio Copper Co., United States & Lark, and National Tunnel & Mines Co. properties in the Bingham district and the Tintic Standard property in the Tintic district.

During the first 3 months of 1943, Utah mines were producing copper at a rate calculated to exceed the record output of 1942 by at least

15,000,000 pounds.

Lead.—Mine production of recoverable lead in Utah was 143,860,000 pounds in 1942, compared with 139,202,000 pounds in 1941. The Bingham district was again the chief source of lead and gained 10,967,300 pounds over 1941. The Park City region output declined for the second successive year. Four properties—the Silver King, Park Utah Consolidated, Mayflower, and Park City Consolidated—together contributed over 95 percent of the total lead output of the region; of these four properties, the Park City Consolidated closed in October, and only the Mayflower made an increase over 1941. The lead output of the Tintic district gained, owing primarily to increased production at the Tintic Standard mine. Output from the Calumet mine, chief producer in Tooele County, decreased in 1942. The United States & Lark properties in the Bingham district continued to be the largest source of lead in the State, followed by the Silver King Coalition, Tintic Standard, Park Utah Consolidated, Calumet, Mayflower, and Chief Consolidated; these seven producers supplied 85 percent of the State total output of lead.

Production reports during the first 3 months of 1943 indicate that the recoverable lead output of Utah will be higher in the year 1943

than it was in 1942.

Zinc.—Output of recoverable zinc from Utah ores and slags amounted to 91,086,000 pounds in 1942 compared with 84,098,000 in 1941. Zinc recovered from old and current slag fumed accounted for the gain, as zinc recovered from zinc-lead ore declined. As in former years, the bulk of the recovered zinc came from ores of the Bingham district and Park City region, and although there was a gain in zinc output in the Bingham district it was more than

offset by losses in the Park City region. Substantial gains were noted in the output of zinc from the Tintic district in 1942, but the district is still of minor importance compared with the Bingham and Park All the zinc and zinc-lead concentrates produced in Utah in 1942 were treated at plants of the Anaconda Copper Mining Co. at Anaconda and Great Falls, Mont. Zinc fume derived from the fuming of current slag, old slag, and a small quantity of zinc ore was first deleaded and then shipped to Hillsboro, Ill., and Bartlesville, Okla., for further treatment. The zinc recovered from the fuming of current slag has not been credited entirely to Utah; the zinc ultimately recovered in the fuming operation, which originates in ores and concentrates containing at least 10 percent zinc, has been credited to the State of origin. The principal producers of zinc in Utah in 1942, named in order of output, were: United States & Lark mines, Tooele slag-fuming plant, Silver King Coalition, Park Utah Consolidated Mining Co., Mayflower, Calumet, Chief Consolidated properties, Park City Consolidated Mining Co. (closed in October 1942), and Butterfield group; these nine properties produced 97 percent of the State total zinc output.

According to calculations based on reports received during the first 3 months of 1943, the recoverable zinc output of Utah in 1943 will exceed that in 1942 by about 6,000,000 pounds.

## MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in Utah in 1942, by counties, in terms of recovered metals

County -	Mines producing		Ore (short	Gold (lode	and placer)	Silver (lode and placer)		
Lode	Lode	Placer	tons)	Fine ounces	Value	Fine ounces	Value	
Beaver Box Elder Grand	10 2	2	12, 653 102	365 3 7	\$12,775 105 245	44, 571 45	\$31, 695 32	
Iron Juab Millard Morgan	18 3 1	1	1, 558 166, 193 434 1	210 10, 437 84	7, 350 365, 295 2, 940	1, 108 720, 834 1, 028	788 512, 593 731	
Piute Salt Lake San Juan Sevier	3 23 1	1	964 34, 088, 363 69 10	291 327, 390 8 22	10, 185 11, 458, 650 280 770	10, 066 5, 416, 671 24 914	7, 158 3, 851, 855 17 650	
Summit Pooele Uintah	11 26	2	182, 124 259, 164	5, 104 16, 349 14	178, 640 572, 215 490	1, 293, 255 399, 247	919, 648 283, 909	
Utah Wasatch Washington Wayne	15 4 2 1		171, 756 97, 624 636 4	13, 422 17, 831 7	469, 770 624, 085 245	1, 346, 729 1, 338, 854 1, 585 24	957, 674 952, 074 1, 127 17	
rotal, 1941	123 167	6 12	34, 981, 655 31, 952, 817	1 391, 544 2 356, 501	13, 704, 040 12, 477, 535	10, 574, 955 11, 395, 485	7, 519, 968 8, 103, 456	

<sup>&</sup>lt;sup>1</sup> Includes 32 ounces of placer gold distributed as follows: Grand County, 7 ounces; Millard County, 3 ounces; San Juan County, 8 ounces; and Uintah County, 14 ounces.

<sup>2</sup> Includes 629 ounces of placer gold distributed as follows: Garfield County, 4 ounces; Grand County, 252 ounces; Millard County, 21 ounces; San Juan County, 18 ounces; and Uintah County, 334 ounces.

Mine production of gold, silver, copper, lead, and zinc in Utah in 1942, by counties, in terms of recovered metals—Continued

	Copper		Le	ad	Zi	ne	(Data) l
County	Pounds	Value	Pounds	Value	Pounds	Value	Total value
Beaver Box Elder Grand	107, 800 1, 000	\$13, 044 121	627, 000 17, 300	\$42,009 1,159	291, 700 16, 000	\$27, 128 1, 488	\$126, 651 2, 906 245
Iron Juab Millard Morgan	300 540, 000 15, 300	36 65, 340 1, 851	25, 300 6, 097, 000 1, 000 300	1, 695 408, 499 67 20	3, 143, 000 88, 000	292, 299 8, 184	9, 869 1, 644, 026 13, 773
Piute Salt Lake San Juan Sevier	2, 200 609, 420, 000 5, 700	73, 739, 820 690	58, 300 80, 121, 000	3, 906 5, 368, 107	6, 000 45, 358, 000	558 4, 218, 294	22, 073 98, 636, 726 987 1, 420
Summit Tooele Uintah	756, 700 477, 000	91, 561 57, 717	22, 516, 400 11, 973, 400	1, 508, 599 802, 218	18, 624, 700 15, 735, 000	1, 732, 097 1, 463, 355	4, 430, 544 3, 179, 414 490
Utah Wasatch Washington Wayne	1, 168, 000 698, 000 190, 000	141, 328 84, 458 22, 990	14, 342, 000 8, 040, 400 40, 600	960, 914 538, 707 2, 720	396, 600 7, 427, 000	36, 884 690, 711	2, 566, 570 2, 890, 035 27, 082
Total, 1941	613, 382, 000 533, 676, 000	74, 219, 222 62, 973, 768	143, 860, 000 139, 202, 000	9, 638, 620 7, 934, 514	91, 086, 000 84, 098, 000	8, 470, 998 6, 307, 350	113, 552, 848 97, 796, 623

#### MINING INDUSTRY

The production of copper ore (96 percent of the State total ore) dominated the mining industry in Utah in 1942. The Bingham district produced ore of all classes, representing 97 percent of the State total. Of the 34,087,179 tons of ore produced in the Bingham district in 1942, copper ore constituted 99 percent; virtually all the remainder was zinc-lead ore and lead ore. The grade of the copper ore and zinc-lead ore was about the same as in 1941. The bulk of the ore mined in the Park City region in 1942 was zinc-lead ore; this ore showed a lowering of zinc, lead, and silver content compared with 1941. The Tintic district again made a large gain in output of zinc-lead ore, but almost all was mined from the lower workings of the Chief Consolidated properties. The output and grade of zinc-lead ore mined in Tooele County decreased. Production of siliceous ore declined from 1941, and much of the output came from old mine and tailings dumps; the largest decline was noted in gold ore from Tooele County. The Camp Floyd district in Tooele County and the Tintic district in Juab and Utah Counties supplied 87 percent of the siliceous ore of the State.

#### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

The Contract of the Contract o

Ore sold or treated in Utah in 1942, with content in terms of recovered metals

Source	Mines produc- ing	Ore	Gold	Silver	Copper	Lead	, Zinc
Dry and siliceous gold ore Dry and siliceous gold-silver ore Dry and siliceous silver ore	19 27 21	Short tons 126, 405 224, 420 83, 409	15, 933	879, 892	1, 569, 845	5, 867, 295	
Copper oreLead oreLead-copper oreZinc oreZinc-lead oreZinc-lead-copper ore	67 16 40 1 7 38 3	434, 234 33, 611, 061 75, 758 41 16, 710 2841, 837 2, 014	291, 806 9, 727 6 50, 378	2, 698, 515 786, 550 421 2, 278	1 606, 444, 452 668, 374 1, 813 5, 655 3, 915, 253	118, 779 18, 627, 328 9, 842 13, 552 115, 289, 671	340, 100 90, 372, 500
Total, lode mines Total, placers Total, 1941	129	34, 981, 655 34, 981, 655 31, 952, 817	391, 544	10, 574, 955	1 613, 382, 000 	143, 860, 000	91, 086, 000

Includes 32,062,916 pounds recovered from mine-water precipitates.
 Includes 87,831 tons of zinc-lead slag.
 A mine producing more than I class of ore is counted but once in arriving at total for all classes.
 Includes 13,418,668 pounds recovered from mine-water precipitates.

#### METALLURGIC INDUSTRY

In 1942, mines in Utah produced 34,981,655 tons of ore—the greatest quantity in the history of the State-surpassing the former record of 1941 by 3,028,838 tons. This total was treated as follows: 34,336,812 tons at concentrating mills compared with 31,205,481 tons in 1941; 94,827 tons at cyanide mills compared with 252,080 tons in 1941; 1,475 tons at amalgamation mills compared with 515 tons in 1941; 460,710 tons shipped crude to smelters compared with 465,083 tons in 1941; and 87,831 tons (zinc-lead slag) fumed compared with 29,658 tons in 1941. A considerable tonnage of siliceous ore, included in the quantity shipped crude to smelters, came from old dumps and tailings piles and was used primarily as a flux in smelting. tailings usually were paid for according to metal content, so that the shipper would be eligible for any premium payments allowed by the Government; however, smelters at times allowed extra payments for very high silica content.

All ore cyanided was handled by two cyanide plants at Mercur, under control of Snyder Mines, Inc., and all cyanide operations were discontinued after September 17. The total of 94,827 tons of gold ore cyanided yielded 7,426 ounces of gold and 157 ounces of silver; Snyder Mines, Inc., reported the consumption of 70,000 pounds of calcium cyanide, 7,500 pounds of zinc dust, and 634,000 pounds of Eleven concentrating plants were active in Utah during 1942 four plants (Arthur, Magna, Ohio Copper, and Tooele) treated 33,565,587 tons of copper ore and old tailings; four mills (Bauer, Midvale, Silver King, and Tooele), with a combined rated capacity of 4,400 tons, treated 754,925 tons of ore mostly zinc-lead, zinc-lead. copper, and zinc; two gravity-concentration mills (Tooele County and Utah County) treated 300 tons of lead and silver ores; and one flotation mill in Summit County treated 16,000 tons of old zinc-lead tailings.

Three lead and two copper smelters were active in Utah in 1942. The combined rated capacity of the lead smelters was about 1,130,000 tons of charge a year, and that of the copper smelters was 1,900,000 tons. In 1942 the smelting capacity of Utah smelters was never reached, but during the summer and early fall a labor shortage at the Garfield smelter caused the American Smelting & Refining Co. to ship a portion of its receipts of copper concentrates to Tooele, Tacoma, and El Paso smelters. The Murray lead smelter was down part of the year owing to lack of ore and concentrates.

The following tables give details of treatment for all the ore produced

in Utah in 1942.

Mine production of metals in Utah in 1942, by methods of recovery, in terms of recovered metals

Method of recovery	Material treated	Gold	Silver	Copper	Lead	Zine
Ore amalgamated	Short tons 1, 475 94, 827	Fine ounces 95 7,426	Fine ounces 61 157	Pounds	Pounds	Pounds
Concentrates smelted_ Slag fumed Ore smelted	1, 187, 858 87, 831 460, 710	338, 534 45, 457	7, 859, 726 2, 715, 011	576, 299, 466 5, 019, 618	115, 471, 084 28, 388, 916	90, 613, 800 472, 200
Mine-water precip- itates smelted 1 Placer	18, 813	32		32, 062, 916		
Total, 1941		391, 544 356, 501	10, 574, 955 11, 395, 485	613, 382, 000 533, 676, 000	143, 860, 000 139, 202, 000	91, 086, 000 84, 098, 000

<sup>1</sup> All from Salt Lake County.

Mine production of metals from concentrating mills in Utah in 1942, by counties, in terms of recovered metals

			Concent	rates smelte	d and recove	red metal	
County	Ore milled	Concen- trates produced	Gold	Silver	Copper	Lead	Zinc
Beaver Juab Piute Satt Lake Summit Tooele Utah Wasatch	Short tons 3, 249 26, 473 68 34, 004, 884 165, 679 38, 464 3, 201 94, 794	Short tons 699 6, 406 33 1, 096, 615 42, 274 17, 686 1, 031 23, 107	Fine ounces 35 459 5 314, 411 4, 396 1, 441 129 17, 498	Fine ounces 11, 292 65, 682 712 5, 128, 636 1, 152, 925 244, 757 9, 170 1, 237, 720	Pounds 3, 503 342 574, 806, 522 664, 085 148, 118 6, 028 663, 868	Pounds 201, 940 1, 570, 194 13, 395 76, 596, 894 21, 245, 598 6, 097, 168 376, 363 7, 656, 432	Pounds 270, 000 3, 015, 000 6, 000 45, 271, 300 18, 624, 700 4, 355, 900 395, 600 7, 427, 000
Total, 1941	34, 336, 812 31, 205, 481	1, 187, 851 1, 073, 438	338, 374 286, 571	7, 850, 894 7, 971, 032	576, 292, 466 516, 363, 067	113, 757, 984 108, 538, 218	79, 365, 500 80, 906, 987

Gross metal content of concentrates produced from ores mined in Utah in 1942, by classes of concentrates smelled

ctusses of concentrates smetted											
Class of concentrates	Concen- trates pro-	Gross metal content									
	duced	Gold	Silver	Copper	Lead	Zinc					
Dry gold 1	Short tons	Fine ounces	Fine ounces	Pounds	Pounds	Pounds					
Copper	894, 954	288, 093	2, 651, 763	587, 015, 624	34, 134	19,602					
Lead-copper.	88, 352 5, 576	14, 976 6, 419	3, 562, 277 459, 544	2, 616, 802 514, 570	97, 776, 393 5, 975, 712	8, 390, 452 792, 651					
Zinc	35, 803	4, 201	319, 299	372, 950	1, 855, 430	40, 027, 965					
Zinc-lead	47, 492	5,069	330, 324	907, 281	7, 139, 584	48, 156, 359					
ore)	115, 674	19,616	527, 687	762, 568	6, 857, 656	5, 396, 977					
Total, 1941	1, 187, 858 1, 073, 438	338, 510 286, 571	7,851,851 7,971,032	592, 189, 795 533, 304, 098	119, 638, 909 113, 909, 900	102, 784, 006 102, 626, 120					
	1	I	!	I		í					

<sup>1</sup> From 1,445 tons of ore amalgamated and concentrated.

Mine production of metals from Utah concentrates shipped to smelters in 1942, in terms of recovered metals

#### BY COUNTIES

	<u> </u>	<b>D1</b> 00	ONTIES			
	Concen- trates	Gold	Silver	Copper	Lead	Zinc
Beaver Iron 1	Short tons	Fine ounces	Fine ounces 11, 292	Pounds 3, 503	Pounds 201, 940	Pounds 270, 000
Juab Piute	6, 406 33	136 459 5	957 65, 682 712	342	1, 570, 194 13, 395	3, 015, 000 6, 000
Salt Lake Summit Fooele	42, 274 17, 686	314, 411 4, 396 1, 441	5, 128, 636 1, 152, 925 244, 757	574, 806, 522 664, 085 148, 118	76, 596, 894 21, 245, 598 6, 097, 168	45, 271, 300 18, 624, 700 4, 355, 900
Utah Wasatch	1, 031 23, 107	129 17, 498	9, 170 1, 237, 720	6, 028 663, 868	376, 363 7, 656, 432	395, 600 7, 427, 000
Total, 1941	1, 187, 858 1, 073, 438	338, 510 286, 571	7, 851, 851 7, 971, 032	576, 292, 466 516, 363, 067	113, 757, 984 108, 538, 218	79, 365, 500 80, 906, 987
	BY CLAS	SES OF CO	NCENTRA	TES SMEL	red	
Dry gold 1	7	136	957			
Copper	894, 954	288, 093	2, 651, 763	572, 317, 467	18, 575	
LeadLead_copper	88, 352	14, 976	3, 562, 277	1,841,642	93, 865, 433	
Zine	5, 576 35, 803	6, 419 4, 201	459, 544 319, 299	349, 256 353, 640	5, 736, 684 1, 688, 443	36, 024, 700
Zinc-lead Dry iron (from zinc-lead	47, 492	5,069	330, 324	861, 918	6, 497, 021	43, 340, 800
ore)	115, 674	19, 616	527, 687	568, 543	5, 951, 828	
	1, 187, 858	338, 510	7, 851, 851	576, 292, 466	113, 757, 984	79, 365, 500

<sup>1</sup> From 1,445 tons of ore amalgamated and concentrated.

Gross metal content of Utah crude ore shipped to smelters in 1942, by classes of ore

Class of ore	0	Gross metal content						
Class of ore	Ore	Gold	Silver	Copper	Lead	Zine		
Dry and siliceous gold. Dry and siliceous gold-silver. Dry and siliceous silver. Copper. Lead. Lead-copper. Zinc-lead. Zinc-lead-copper.	Short tons 30, 103 224, 420 83, 309 45, 474 75, 489 41 391 1, 207 276	Fine ounces 12, 931 15, 933 3, 059 3, 716 9, 724	Fine ounces 34, 639 879, 892 959, 839 48, 779 786, 026 421 187 3, 839 1, 389	Pounds 62, 272 1, 610, 322 629, 513 2, 142, 903 905, 838 2, 290 1, 813 2, 973 20, 328	Pounds 413, 588 9, 700, 124 5, 259, 228 197, 490 20, 241, 940 11, 069 3, 139 277, 954 39, 687	Pounds		
Total, 1941	460, 710 465, 083	45, 457 51, 458	2, 715, 011 3, 422, 061	5, 378, 252 4, 253, 415	36, 144, 219 38, 095, 332	705, 479 230, 630		

Mine production of metals from Utah crude ore shipped to smellers in 1942, in terms of recovered metals

#### BY COUNTIES

	Ore	Gold	Silver	Copper	Lead	Zinc
	Short	Fine	Fine			
	tons	ounces	ounces	Pounds	Pounds	Pounds
Beaver	9, 384	314	33, 279	104, 297	425, 060	21, 700
Box Elder		3	45	1,000	17, 300	16,000
Iron		1	90	300	25, 300	
Juab	139, 720	9,978	655, 152	540,000	4, 526, 806	128,000
Millard		81	1,028	15, 300	1,000	88,000
Morgan	1				300	
Piute	896	286	9, 354	1,858	44, 905	
Salt Lake	83, 479	12,979	288, 035	2, 550, 562	3, 524, 106	86, 700
San Juan	_ 69		24	5, 700		
Sevier	. 10	22	914			
Summit	16, 445	708	140, 330	92, 615	1, 270, 802	
Tooele		7, 458	146, 458	321,882	4, 163, 132	130, 800
Utah	168, 555	13, 293	1, 337, 559	1, 161, 972	13, 965, 637	1,000
Wasatch		333	101, 134	34, 132	383, 968	
Washington		1	1, 585	190,000	40,600	
Wayne	_ 4		24			
	400 510	45 455	0.715.011	5, 019, 618	28, 388, 916	472, 200
m 1 . 1041	460, 710	45, 457	2, 715, 011	3, 892, 765	30, 306, 782	177, 01
Total, 1941	465, 083	51, 458	3, 422, 061	5, 892, 100	30, 300, 732	177,010
	BY CI	LASSES O	F ORE			
Dry and siliceous gold	30, 103	12, 931	34, 639	60, 200	276, 976	
Dry and siliceous gold-silver	224, 420	15, 933	879, 892	1, 569, 845	5, 867, 295	
Dry and siliceous silver	83, 309	3,059	959, 839	612, 238	3, 225, 914	
Copper	45, 474	3, 716	48, 779	2, 088, 488	118,779	
Lead		9,724	786, 026	668, 374	18, 588, 939	l
Lead-copper	41		421	1,813	9,842	
Zinc	391		187	1, 471	2, 690	126, 70
Zinc-lead	1, 207	93	3, 839	1,943	259, 508	266, 80
Zinc-lead-copper		1	1,389	15, 246	38, 973	78, 70

REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, lead, and zinc in Utah in 1942, by counties and districts, in terms of recovered metals

O A district	Mines p	roducing	Ore sold or				Silver (all	Copper	Lead	Zine	Total
County and district	Lode	Placer	treated	Lode	Placer	Total	lode)	Сорры			value
Beaver County: Beaver Lake	1		Short tons	Fine ounces	Fine ounces	Fine ounces 2 17	Fine ounces 187	Pounds 12, 600	Pounds 1,600	Pounds	\$1,83 59
Newton	1 2 4 2		21 686 11, 249 542	17 13 328 5		13 328 5	1, 094 41, 580 1, 710	49, 700 40, 200 5, 300	582, 400 42, 400	149, 000 142, 700	7, 28 98, 79 18, 14
Box Elder County: Crater Island Promontory Grand County: Colorado River	1	2	25 77	3	7	3 7	24 21	1,000	17, 300	16,000	2, 66 24
Iron County: Indian Peak (formerly called Calumet)	1 1		113 1, 445.	1 209		1 209	90 1,018	300	25, 300		1, 83 8, 03
Jusb County: Detroit <sup>1</sup> Fish Springs Mount Nebo	1 1 1		114 51 7	34 1		34 1	128 4,365 31	100 539, 900	100 32, 400 2, 600 6, 061, 900	3, 128, 000	1, 30 5, 31 19 1, 635, 78
Tintic <sup>2</sup>	14 1 2		165, 980 41 201	10, 402 		10, 402	716, 251 59 1, 021	15, 300		15, 000	1,4 5,4
House Mountain Kanosh Morgan County: Argenta	1	1	233		3	3	7		1, 000 300	88,000	8, <b>2</b>
Mount BaldyOhio	2		288 676	242 49		242 49 80	5, 438 4, 628 15, 006	400 1,800 43,300	5, 600 52, 700 89, 700	6,000 90,900	12, 70 9, 3 33, 1
Big Cottonwood	2		989 88 107 34, 087, 179	26 26 327, 258		26 26 327, 258	15,006 872 1,049 5,399,744	700 1, 100 609, 374, 900	19,000 21,000 79,991,300	45, 267, 100	2, 8 3, 1 98, 597, 4
San Juan County: Colorado River La Sal		1	69		8	8	24	5, 700			27

See footnotes at end of table.

GOLD, SILVER, COPPER, LEAD, AND ZINC IN UTAH

Mine production of gold, silver, copper, lead, and zinc in Utah in 1942, by counties and districts, in terms of recovered metals—Continue

	Mines p	roducing	Ore sold or	Gold			Silver (all	Copper	Lead	Zinc	Total
County and district	Lode	Placer	treated	Lode	Placer	Total	lode)				value
Sevier County: Henry. Summit County: Uintah. Tooele County: Camp Floyd. Clifton. Dugway. Erikson. Lakeside. North Tintic. Ophir. Rush Valley. "Smelter" Willow Springs. Uintah County: Green River. Utah County: American Fork. Tintic? Wasatch County: Blue Ledge. Snake Creek. Washington County: Buil Valley. Tutsagubet. Wayne County: Hanksville.	11 6 1 1 1 2 1 6 5 1 2 2 1 0 2 1 2 1 1 2 1 2 1 1 2 1 1 2 1 2	2	Short tons 10 182, 124 115, 925 8 330 21 1, 059 11, 245 41, 494 87, 831 1, 142 596 171, 160 47, 596 50, 028 10 626 4	90 1, 915 1, 875 13, 417 3, 419 14, 412 6 1	14	90 1, 915 1, 875 14 13, 417 3, 419 14, 412 6	Fine ounces 914 1, 293, 255 914 59 391 107 585 69 134, 602 253, 523 9, 007 3, 787 1, 342, 942 750, 531 588, 323	Pounds 756, 700 100 403, 200 71, 000 2, 700 1, 166, 800 181, 000 517, 000		Pounds  18, 624, 700  56, 300 2, 300 11, 400 8, 700 378, 380 15, 249, 300 28, 700  108, 700 287, 900 2, 036, 300 5, 390, 700	\$1, 420 4, 430, 545 436, 855 343 7, 626 913 13, 228 1, 695 400, 291 2, 208, 503 109, 960 490 16, 633 2, 549, 937 1, 012, 770 1, 877, 265
Total Utah	123	6	34, 981, 655	391, 512	32	391, 544	10, 574, 955	613, 382, 000	143, 860, 000	91, 086, 000	113, 552, 848

Detroit district lies in both Juab and Millard Counties.
 Tintic district lies in both Juab and Utah Counties.

#### BEAVER COUNTY

Beaver Lake district.—A shipment of silver-lead ore and copper ore from the O. K. mine comprised the only output from the Beaver Lake district in 1942.

Newton district.—Gold ore amalgamated and gold ore shipped crude to a smelter from the Walkover mine comprised the output

from the Newton district in 1942.

Rocky district.—D. E. Kirk, lessee on the Montreal mine, shipped several cars of crude silver-copper ore direct to the Garfield smelter. The only other production was from the Old Hickory group, from which 4 cars of silver-copper ore were shipped direct to Garfield; the Old Hickory group is operated primarily for the tungsten in the ore.

San Francisco district.—Hall Bros. Co., Inc., largest producer in the San Francisco district, began operation on the Horn Silver mine and dump in May 1942 and continued the rest of the year. Crude gold-silver-lead ore was shipped direct to Garfield and zinc-lead ore to Bauer. Other production in the district came from the Imperial group, Mayflower, and Quad Metals mines.

Star and North Star district.—Moscow Silver Mines shipped crude zinc ore direct to the Tooele smelter and mill, and lessees shipped

crude lead ore direct to Murray from the Wild Bill dump.

#### BOX ELDER COUNTY

Crater Island district.—A small lot of copper ore was shipped to Tooele from the Copper Blossom mine in 1942.

Promontory district.—Some crude zinc-lead ore was shipped direct to Tooele from the Lake View Carbonate mine by lessees in 1942.

#### IRON COUNTY

Indian Peak district (formerly called Calumet).—The New Arrow-head Mining Co. shipped crude lead ore direct to smelters in 1942 and supplied the only output from the Indian Peak district.

Stateline district.—Gold ore treated in the amalgamation-flotation mill of Etna Gold Mines, Inc., comprised the only production from the

Stateline district in 1942.

#### JUAB COUNTY

Detroit district.—The Detroit district lies in both Juab and Millard Counties, and in 1942 the only output from the Juab County section was crude gold ore shipped to the Garfield smelter from the Clara B. and First Chance claims.

Fish Springs district.—The Utah Mine group was operated intermittently in 1942 by lessees, and the only production was a car of

silver-lead ore shipped crude to Murray.

Mount Nebo district.—Lead cre shipped direct to a smelter from the Central Sultana group was the only output in the Mount Nebo

district in 1942.

Tintic district.—The Tintic district, which lies in both Juab and Utah Counties, is reviewed here. The table that follows gives the metal production in each section of the district in 1942, a comparison with the total in 1941, and the grand total from 1869 to 1942.

Mine production of gold, silver, copper, lead, and zinc in Tintic district, Juab and Utah Counties, Utah, 1941-42, and total, 1869-1942, in terms of recovered metals

	Mines pro- ducing	Ore	Gold	Silver	Copper	Lead	Zinc	Total value
1942 Juab County Utah County	10	Short tons 165, 980 171, 160	13, 417	Fine ounces 716, 251 1, 342, 942				
Total, 1941 Total, 1869-1942		337, 140 349, 343 (1)	23, 950	2, 059, 193 2, 711, 790 255, 484, 367	2, 084, 300		1, 594, 000	4, 206, 513

<sup>1</sup> Figures not available.

In 1942 the Chief Consolidated Mining Co. operated the Chief No. 1, Gemini, Eureka Hill, and Plutus mines in Juab County. Although the bulk of the production in 1942, as in 1941, came from the Chief No. 1 mine, substantial tonnages of siliceous ores were shipped to the Garfield smelter from the Gemini mine; the production from the Eureka Hill (all siliceous ore) was materially smaller than in 1941, but that from the Plutus mine was about the same. The Chief No. 1 has large bodies of zinc-lead ore, which in 1941 were under water. After the company was granted favorable quotas and assured a premium price for the recoverable zinc and lead by the Government, an extensive dewatering program was begun. According to the company printed annual report, dewatering these lower levels of the Chief No. 1 mine and equipping and opening up the connecting winzes, all in an area of 2,000 by 800 feet, comprised most of the development work in 1942. Inasmuch as mining has now begun in this area, the company anticipates that by progression it will finally reach a mined tonnage of zinc-lead ore of over 5,000 tons per month. The ore consists predominantly of sulfides and contains about 3.5 percent lead and 7.5 percent zinc. Production in 1942, says the report, comprised 38,612 tons of siliceous ore, 671 tons of silver-lead ore, and 27,093 tons of zinc-lead ore from the Chief No. 1 mine; 6,312 tons of siliceous ore and 1,118 tons of silver-lead ore from the Gemini mine; 172 tons of siliceous ore from the Eureka Hill mine; and 795 tons of siliceous ore and 59 tons of silver-lead ore from the Plutus mine—an aggregate of 74,832 tons of ore of all classes, containing 2,867 ounces of gold, 290,666 ounces of silver, 100,539 pounds of copper, 5,271,482 pounds of lead, and 4,605,698 pounds of zinc.

The Eagle & Blue Bell, Centennial-Beck, and Victoria mines, all owned or controlled by the United States Smelting, Refining & Mining Co., were operated on company account throughout 1942. The production from these properties comprised 18,573 tons of siliceous ore, 2,274 tons of lead ore, and 112 tons of zinc-lead ore, all of which was shipped crude to smelters. The Empire group, controlled by the International Smelting & Refining Co., was operated by lessees throughout the year. Production amounted to 2,229 tons of crude gold-silver ore shipped direct to a smelter. Philip P. Clark, lessee on the Godiva mine, shipped 27,056 tons of siliceous ore and tailings to Garfield and 183 tons of lead ore to Murray. A considerable quantity of siliceous tailings and crude ore was shipped direct to the Garfield smelter from the Mammoth mine in 1942, and some zinc-lead ore was shipped to the Tooele slag-fuming plant. The

いると文字ととならいと言語

remainder of the output from the Juab County section of the Tintic district was predominantly siliceous ore and tailings, all of which was

shipped crude to smelters.

The Tintic Standard Mining Co. and its subsidiary companies were again the largest producers in the Utah County section of the Tintic district. The printed annual report of these companies gives the following operating details. At the Tintic Standard mines (including the Iron Blossom) production of siliceous gold-silver ore was drastically reduced from 75,744 tons in 1941 to 36,433 tons in 1942, all of which was mined on company account; lessees produced an additional 2,086 tons of siliceous ore. This reduction was necessary because no premium payments of importance would be received on these ores owing to their low content in lead and copper. Output of lead ore was increased from 31,199 to 40,379 tons, and the lead content increased from 7,794,650 to 10,234,549 pounds. Siliceous dump ore totaling 3,891 tons was shipped from the Eureka Standard mine. Lease operations were carried on throughout 1942 on the Colorado mine, and 2,176 tons of siliceous ore were shipped direct to a smelter. At the Eureka Lilly mine ore bodies developed near the Eureka Lilly shaft were mined, and further increased production from this area can be expected.

An agreement was made between the Tintic Standard Mining Co. and the North Lily Mining Co. (operating subsidiary of the International Smelting & Refining Co.) whereby a joint operation, known as the Development Unit, was carried on for the purpose of developing portions of the Twentieth Century Mining Co. ground, in which the North Lily Mining Co. is interested, and portions of the Eureka Lilly Mining Co. property, which is controlled by the Tintic Standard The Tintic Standard report states that the most im-Mining Co. portant work carried on during the year was the joint development with the North Lily Mining Co. The work was done from the Tintic Standard 1,450-foot level and comprised 2,568 feet of drifts and 110 feet of raises. Up to February 1943 only diamond drilling had prospected the limestone area. Good ore was encountered in one drill hole and in a vein found in a crosscut from the main drift; work is progressing at this time to further the development of these During the operation in 1942 production amounted to deposits. 1.707 tons of siliceous ore and came from that portion of the Development Unit controlled by the Eureka Lilly Mining Co.

The tonnage of ore of all classes mined by the Tintic Standard Mining Co. and its subsidiary companies, including ore from the Development Unit, aggregated 93,874 tons with the following metal content: 4,436 ounces of gold, 1,130,459 ounces of silver, 1,052,259 pounds of copper, 12,677,062 pounds of lead, and 1,295 pounds of zinc. The Harold dump of the Tintic Standard Mining Co. was worked by the American Smelting & Refining Co., and 68,980 tons of siliceous ore was shipped direct to the Garfield smelter in 1942; the ore contained over 3,500,000 pounds of lead. Active mines in the Utah County section of the Tintic district, owned or controlled by the International Smelting & Refining Co. and its subsidiaries, were the Tintic Bullion, May Day (Mountain View), Hanibal, and North Lily; these properties were operated throughout the year and produced 3,510 tons of silice-

ous ore and 2,606 tons of zinc-lead ore.

Trout Creek district.—The Trout Creek Mining Co. shipped a car of zinc ore to the Combined Metals Reduction Co. plant at Bauer.

### MILLARD COUNTY

Detroit district.—Some copper ore was shipped crude to a smelter

from the R. L. Laws and Gold Chief properties in 1942.

Kanosh district.—The Kanosh Leasing Co., operating the Blue Bell mine, shipped some crude zinc ore direct to the Tooele slag plant in 1942.

## MORGAN COUNTY

Argenta district.—A test lot of lead ore was shipped crude to the Midvale smelter from the Carbonate Gem mine in 1942.

### PIUTE COUNTY

Mount Baldy district.—John Pearson, lessee, operated the Deer Trail mine all of 1942 and shipped crude gold-silver ore direct to the Garfield smelter.

Ohio district.—Output from the Ohio district in 1942 was many times that in 1941 and comprised gold-silver ore and lead ore from the Bully Boy mine shipped crude to smelters and zinc-lead ore from Cascade Lot 57 shipped to the Midvale concentrator.

### SALT LAKE COUNTY

Big and Little Cottonwood districts.—Base-metal ore shipped direct to smelters from the Cardiff mine supplied most of the output from the Big Cottonwood district in 1942. It included 335 tons of copper ore, 128 tons of lead ore, and 202 tons of zinc-lead ore. The Mountain Mines Co. produced 304 tons of siliceous ore which was shipped crude to the Garfield smelter. Other production in the district came from the property of the Kentucky-Utah Mining Co. and from the Richmond Teresa and Kennebec mines.

Crude lead ore from the Columbus Rexall Consolidated Mines Co. and Wasatch Mines Co. shipped direct to a smelter comprised the

output from the Little Cottonwood district in 1942.

"Smelter" district.—Output from the "Smelter" district in 1942 came chiefly from the Germania dump, clean-ups at local assay offices,

and clean-up of railroad yards and tracks.

West Mountain (Bingham) district.—The Bingham district, by far the most important mining region in Utah, produced over four-fifths of the gold, virtually all of the copper, and over half of the lead, silver, and zinc output of the State in 1942. The following table shows production from mines in the district in 1941 and 1942 and the total from 1865 to 1942.

Mine production of gold, silver, copper, lead, and zinc in Bingham or West Mountain district, Salt Lake County, Utah, 1941-42, and total, 1865-1942, in terms of recovered metals

Year	Mines pro- ducing	Оге	Gold (lode and placer)	Silver (lode and placer)	Copper	Lead	Zinc	Total value
1941 1942 Total, 1865–1942		Short tons 30, 866, 163 34, 087, 179 (1)	327, 258	5, 399, 744	Pounds 529, 409, 000 609, 374, 900 2 3, 730, 607	79, 991, 300	45, 267, 100	\$82, 558, 340 98, 597, 468 1, 466, 333, 507

<sup>1</sup> Figures not available.

<sup>2</sup> Short tons.

The Utah Copper Co. easily maintained its position as the largest copper producer in the world and in 1942 surpassed by a wide margin its previous record output. The company produced over two-thirds of the State gold, about one-quarter of the State silver, and nearly all of the State copper. Ore was milled at the two flotation-concentration plants (Magna and Arthur units) at an average rate of over 91,000 tons a day compared with about 83,000 tons in 1941. ore milled in 1942 had a slightly higher gold and silver content but a somewhat lower copper content. Mill recoveries of gold and silver were about the same as in 1941, but the average copper recovery increased about 1.5 percent. The output of molybdenum sulfide, a byproduct of the copper production, was considerably greater than Mill recovery of byproduct molybdenum was also higher in 1941. The Magna mill was operated without a shut-down throughout the year, but the Arthur mill lost the equivalent of 6 days of operation. Copper ore and waste were mined at the open pit at Bingham, 17.5 miles from the Magna and Arthur concentrators, at the rate of 204,000 tons a day, which was about 16,000 tons greater than the rate in 1941. The waste was piled in gulches adjacent to the open pit and there leached. In addition to the huge quantity of copper contained in the copper concentrates produced in 1942, over 31,000,000 pounds of copper were contained in the copper precipitates made in the precipitating plant at Lead Mine. Owing to the vast quantities of gold, copper, and molybdenum produced in 1942, the Utah Copper Co. was the leading copper producer and the second-largest molybdenum producer in the United States and ranked high among the gold producers. According to reports received during the first 3 months of 1943, the company is again surpassing any previous output.

The Boston Consolidated property, owned by the Utah Copper Co., was operated all of 1942 by the American Smelting & Refining Co. Crude copper and lead ore was shipped direct to smelters.

Zinc and lead output of the Bingham district, which made notable gains compared with 1941, came largely from the United States & Lark property of the United States Smelting, Refining & Mining Co. In 1942 the company mined and shipped to its Midvale flotationconcentrator about 18 percent more zinc-lead ore than in 1941, of about the same gold, silver, and zinc content but of a slightly higher Crude gold-silver and lead ores shipped direct to a lead content. smelter amounted to about 26,000 tons. The mine was easily the largest producer of lead and the second-largest producer of zinc in the The gold and silver output was exceeded only by Western States. that of the Utah Copper Co. Extensive development work completed in 1942 comprised 20,911 feet of shafts, drifts, and raises and 1,464 feet of diamond drilling. Reports received during the first 3 months of 1943 indicated that in 1943 the company will produce slightly more zinc than in 1942 and about the same quantity of lead. Other properties owned or controlled by the United States Smelting, Refining & Mining Co., active in 1942, included the Niagara, the Montana-Bingham Consolidated, Bingham Metals, and Utah Metal. The total ore of all classes produced from these properties amounted to 20,378 tons in 1942.

The Apex Delaware group was operated the entire year by the National Tunnel & Mines Co. The property, worked through the

Elton tunnel completed in 1941, produced ore of several classes. Output in 1942 of zinc-lead ore was only 5,000 tons, but the rate of production paralleling the development of ore bodies had reached over 1,000 tons a month in December. Development and rehabilitation work on the copper ore bodies of the mine had reached a stage in May 1942 permitting the company to produce copper milling ore at the rate of over 6,000 tons a month; this was gradually increased until in December copper ore was produced at a rate exceeding 10,000 tons a month. In addition to the copper and zinc-lead milling ore produced, 285 tons of gold and lead ores were shipped direct to smelters.

The Ohio Copper Co. treated 410,075 tons of old gravity and flotation tailings, which contained about 8 pounds of copper per ton. From these tailings 4,368 tons of copper concentrates were made, which averaged 25 percent copper. The capacity of the combination acid leaching and flotation mill was increased from 1,000 to 1,500 tons a day. The treatment process involves sluicing the old tailings to the mill. There the pulp is conditioned for half an hour with sulfuric acid; the soluble copper is then precipitated on shredded cans in the pulp. The pulp containing the precipitated copper and sulfide copper then goes through the flotation section of the mill. The resulting concentrate is thickened and filtered.

A total of 26,754 tons of ore of all classes was shipped from the Butterfield group to the Combined Metals Reduction Co. plant at Bauer and to the International Smelting & Refining Co. at Tooele; the total output was about 5,000 tons less than in 1941.

Other producers active in the Bingham district in 1942 included the Bingham Congor, Chicago Silver, Kremlin, Kaighn, and property of the Victory Mines Co.

### SAN JUAN COUNTY

The only lode production from San Juan County in 1942 came from crude copper ore shipped direct to smelter from the Lisbon mine in the La Sal district.

#### SEVIER COUNTY

Henry district.—A small lot of crude gold-silver ore was shipped to Garfield in 1942 from the B. W. & H. property; it comprised the output of the district.

#### SUMMIT AND WASATCH COUNTIES

#### PARK CITY REGION

The Park City region includes the Uintah district in Summit County and the Blue Ledge and Snake Creek districts in Wasatch County. Production of all metals except gold decreased in 1942, as indicated in the following table which gives the output from the region in 1941 and 1942 and the total since 1870.

Mine production of gold, silver, copper, lead, and zinc in Park City region, Summit and Wasatch Counties, Utah, 1941-42, and total, 1870-1942, in terms of recovered metals

Year	Mines pro- ducing	Ore	Gold	Silver	Copper	Lead	Zinc	Total value
1941 1942	12 15	Short tons 337, 595 279, 748	Fine ounces 19, 747 22, 935		Pounds 1, 507, 000 1, 454, 700			
Total, 1870-1942		(1)	496, 320	229, 300, 243	64, 782, 213	2, 318, 503, 634	611, 104, 611	344, 200, 148

<sup>1</sup> Figures not available.

Output from the Silver King Coalition mine and its 800-ton flotation plant was substantially lower than in 1941, owing chiefly to inadequate labor supply. In one period of 1942 employment was only 55 percent of maximum. Under the premium-pay plan the company monthly quota of metal production was set at 567 tons of metallic lead and 472 tons of metallic zinc. As of August 1942 this quota was cut to 150 tons of lead and 125 tons of zinc. The company printed annual report states that mining operations produced 90,824 tons of ore (116,443 in 1941), which comprised 220 tons of crude lead ore and 90,604 tons of zinc-lead milling ore. The latter produced 9,324 tons of lead concentrates and 8,751 tons of zinc concentrates. The total metallic content of the concentrates and crude smelting ore was 1,315 ounces of gold, 854,233 ounces of silver, 452,758 pounds of copper, 12,541,423 pounds of lead, and 10,895,594 pounds of zinc. Development work during 1942 totaled 22,595 feet of drifts, raises, winzes, and shafts; 500 feet of diamond drilling were completed. Recent developments have so improved the physical condition of the property that, assuming an adequate labor supply, 1943 should prove a more productive year.

Consolidated Mines group in Summit County and the Keetley unit in Wasatch County continuously in 1942. All the ore produced was sent to the International Smelting & Refining Co. plants at Tooele for further treatment. According to the company printed annual report, production from the Park Utah Consolidated group of mines was 60,972 tons of ore containing 3,846 ounces of gold, 371,122 ounces of silver, 11,091,618 pounds of lead, 11,425,019 pounds of zinc, and 351,425 pounds of copper. This production was materially lower than in 1941, owing primarily to the shortage of efficient labor and the low price for metals set by the Government for the first 8 months of the year. Some relief was obtained in September 1942, when the premium allowance was adjusted for lead and zinc. mediately after this was granted, operations were changed from a 5-day two-shift to a 6-day two-shift basis, and development footage was increased. Because of the favorable response to this new development, further negotiations for premium revision were started. new negotiations were concluded favorably to the company, and unwatering of the lower levels of the Ontario and Utah units was begun

and the rate of development increased further in horizons above the water level in these two units. If a shortage of manpower does not

The Park Utah Consolidated Mines Co. operated the Park Utah

delay progress, it is expected that enough ore will be uncovered to increase the present rate of production. The Park City Utah Mines group (Keetley unit) in Wasatch County shipped 6,302 tons of ore of all classes to the International mill and smelter for treatment. In addition, the Park Utah Consolidated Mines Co. handled all the operations at the Daly group and shipped about 1,500 tons of zinclead ore to the International mill.

The Park City Consolidated Mines Co. operated in 1942 until August, when the company began closing the property; the final shipment of ore was made October 10. The company reports that during the operating period 40,944 tons of ore were shipped to Midvale and contained 2,299 ounces of gold, 674,024 ounces of silver, 128,287 pounds of copper, 1,460,935 pounds of lead, and 2,542,725 pounds of zinc. Increased operating cost was the stated reason for closing the

property.

Gold-silver-copper-lead-zinc ore shipped to the Midvale concentrator by the New Park Mining Co. amounted to 49,947 tons compared with 58,600 tons in 1941. The ore shipped to Midvale in 1942 was considerably higher in grade; it contained 16,591 ounces of gold, 641,203 ounces of silver, 798,885 pounds of copper, 6,451,642 pounds of lead, and 7,333,470 pounds of zinc, an output surpassing that in 1941 by a wide margin. The company was by far the leading gold producer in the Park City region. Development work completed totaled 4,656 feet of shafts, drifts, crosscuts, and raises and 2,145 feet of diamond drilling. During 1942 ore was developed in the limestones as well as in the igneous (diorite rock) formations.

D. C. Despain operated the American Flag property under lease for 8 months in 1942; during this time 1,490 tons of gold-silver ore were shipped crude to a smelter. A car of silver ore and a car of zinc-lead ore were shipped from the property of the New Quincy

Mining Co.

Old tailings shipped to smelters and old tailings remilled comprised the remaining production from the Park City region in 1942. A total of 27,363 tons of tailings was treated; of this total 16,000 tons were remilled and the zinc-lead middlings produced were shipped to the Midvale concentrator, and 11,363 tons consisted of siliceous silver tailings shipped direct to the Garfield smelter. The most important operations included those of Reuben Garbett, William Wortley, the American Smelting & Refining Co., Marion Lewis, and C. D. Clegg.

#### TOOELE COUNTY

Tooele County ranked fourth among the metal-producing areas in Utah in 1942. Mines in the county produced gold, silver, copper, lead, and zinc valued at \$3,179,414 compared with \$2,892,899 in 1941. This gain was due primarily to output from the Tooele slag-fuming

plant, which more than offset losses from other districts.

Camp Floyd district.—Gold output from the Camp Floyd district, only important straight gold-producing district in Utah, was cut drastically in 1942. The total value of the output was \$436,855 in 1942 compared with \$1,049,610 in 1941. Snyder Mines, Inc., continued to be the largest gold producer in the district and treated over 94,000 tons of ore by cyanidation from both company and custom operations. In addition to the cyanide milling operations, over 21,000

tons of highly siliceous gold ore were shipped direct to Garfield for flux. The smelter continued to receive fluxing material from the Camp Floyd district throughout 1942. The principal producers were Snyder Mines, Inc., and the Sacramento Gold Mining Co.

Clifton district.—A small lot of crude lead ore was shipped direct

to smelters from the Clifton Standard group in 1942.

Dugway district.—Crude lead ore was shipped direct to the International smelter and zinc-lead ore to the Bauer mills from Four Metals Mines, only active property in the district in 1942.

Erickson district.—The Dollar mine produced zinc-lead and lead ore in 1942, which was shipped crude to the International smelter.

Lakeside district.—Output in the Lakeside district in 1942 comprised crude lead ore from the Monarch mine and crude lead ore and zinc-lead ore from the Georgia Lyn mine shipped direct to a smelter, and lead ore milled.

North Tintic district. - Operators of the Scranton mine shipped

crude lead and zinc ore direct to smelters in 1942.

Ophir district.—The total value of metal production from the Ophir district increased in 1942 compared with 1941, owing to the increased output of lead and zinc. The Hidden Treasure mine, largest producer in the district, was operated throughout 1942 by the United States Smelting, Refining & Mining Co.; ore of all classes produced amounted to 6,457 tons, an increase of about 800 tons over 1941. The Star Lease operated the Ophir Queen claim throughout 1942 and shipped lead and zinc-lead ore to the Midvale concentrator and smelter. Several other mines in the district were active in 1942, the most important being the Togo, Ophir Hill, and Mono group.

Rush Valley district.—The West Calumet (Calumet), owned and

Rush Valley district.—The West Calumet (Calumet), owned and operated by the Combined Metals Reduction Co., was in 1942 again by far the largest producer in the Rush Valley district; 36,089 tons (38,455 in 1941) of zinc-lead ore were shipped to the Bauer mill, and 918 tons of crude lead ore were shipped direct to the International smelter. Gold ore was shipped direct to Garfield from the Blue Eagle mine. Other production included ore of several classes from the Silver Eagle mine, lead ore from the Bluestone mine, gold-silver and zinc-lead ores from the Honerine-Galena King, and lead ore from the

Emilie mine.

"Smelter" district.—The International Smelting & Refining Co. operated its slag-fuming plant throughout 1942, and the output of lead and zinc more than trebled compared with 1941. Although the slag-fuming plant treated in all over 119,000 tons of molten slag, cold slag, and crude ore, Utah received production credit for the metal yield from only 87,831 tons; the difference represents material credited to the States in which the original slag-making material originated. The lead blast furnace of the International Smelting & Refining Co. is adjacent to and works in conjunction with the slag furnace. The plants have been thus arranged for convenience of operation as well as to allow the company to extract, with high recoveries, any gold, silver, copper, and lead that are contained in the crude ores, concentrates, old slags, etc., received before the material is treated for the recovery of zinc. The zinc fume produced averaged 71 percent zinc and the lead fume 49 percent lead.

Willow Springs district.—The production in the Willow Springs district came from rich gold ore, lead ore, and zinc-lead ore shipped direct to smelters. The Oro Del Rey mine was by far the outstanding producer.

UTAH COUNTY

American Fork district.—The Dutchman mine was again the largest producer in the American Fork district and in 1942 shipped 299 tons of high-grade zinc-lead ore to Midvale and a few tons of zinc ore to Tooele. Other producers included the Blue Rock and Pacific, Globe,

and Live Yankee mines.

Tintic district.—Mines in the Utah section of the Tintic district are reviewed under Juab County.

# WASHINGTON COUNTY

Bull Valley district.—A little gold ore from the Bull Run mine was amalgamated in 1942.

Tutsagubet district.—Copper ore and lead ore were shipped direct

to smelters from the Apex mine in 1942.

#### WAYNE COUNTY

A test lot of silver ore was shipped direct to a smelter from the Copper Queen mine in the Hanksville district in 1942.

# GOLD, SILVER, COPPER, LEAD, AND ZINC IN WASHINGTON

(MINE REPORT)

By G. E. WOODWARD AND PAUL LUFF

### SUMMARY OUTLINE

Summary. Calculation of value of metal production Mine production by counties. Mining industry	503 506 507	Republic district	512 513
Mining industry Ore classification	507 507	Republic district	513 514

#### SUMMARY

Mines in Washington yielded gold, silver, copper, lead, and zinc valued, in terms of recoverable metal, at \$8,172,609 in 1942 compared with \$7,874,886 in 1941. The output of lead and zinc increased, but that of gold, silver, and copper decreased; the gain in total value of the five metals was due in part to the greater output of lead and zinc and in part to the increase in price paid per unit of recoverable copper, lead, and zinc. The gain in gold production in Chelan County more than offset losses in Ferry, Stevens, and Okanogan Counties. Silver production declined in all the larger producing counties. Almost all the State output of copper was derived, as in former years, from the Holden mine of the Howe Sound Co. in Chelan County. The gain in production of lead and zinc (recovered almost entirely from three mines in Pend Oreille County and two mines in Stevens County) resulted in large measure from the substantially increased output of zinc in Stevens County and of lead in Pend Oreille County. The Pend Oreille Mines & Metals Co. continued as the major producer of both lead and zinc in the State.

All tonnage figures are short tons and "dry weight"; that is, they do not include moisture.

The value of metal production herein reported has been calculated at the following prices.

Prices of gold, silver, copper, lead, and zinc, 1938-42

Year	Gold 1	Silver 2	Copper 3	Lead 4	Zinc 4
1938 1939 1940 1941 1941	Per fine ounce \$35.00 35.00 35.00 35.00 35.00	Per fine ounce  \$ \$0.646+  6.678+  7.711+  7.711+  7.711+	Per pound \$0.098 .104 .113 .118 .121	Per pound \$0.046 .047 .050 .057	Per pound \$0.048 .052 .063 .075

¹ Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.
² Treasury buying price for newly mined silver.
² 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.
¹ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.
¹ \$30.64646464.

Mine production of gold, silver, copper, lead, and zinc in Washington, 1938-42, and total, 1860-1942, in terms of recovered metals

	Mines producing		Ore (short	Gold (lode	and placer)	Silver (lode and placer)		
Year	Lode	Placer	tons)	Fine ounces	Value	Fine ounces	Value	
1938 1939 1940 1941 1942	77 88 83 61 37	80 84 88 56 18	901, 689 1, 124, 564 1, 166, 798 1, 238, 509 1, 222, 937	74, 175 90, 420 82, 136 84, 176 75, 396	\$2, 596, 125 3, 164, 700 2, 874, 760 2, 946, 160 2, 638, 860	380, 938 442, 063 365, 175 402, 030 369, 038	\$246, 263 300, 067 259, 680 285, 888 262, 427	
1860-1942			(1)	1, 957, 121	47, 254, 558	11, 591, 928	8, 203, 574	

	Cor	pper	Le	ad	Zi	Total	
Year	Pounds	Value	Pounds	Value	Pounds	Value	value
1938 1939 1940 1941 1942	12, 034, 000 17, 996, 000 19, 224, 000 17, 372, 000 16, 060, 000	\$1, 179, 332 1, 871, 584 2, 172, 312 2, 049, 896 1, 943, 260	8, 568, 000 7, 436, 000 5, 110, 000 7, 806, 000 9, 702, 000	\$394, 128 349, 492 255, 500 444, 942 650, 034	22, 804, 000 20, 262, 000 23, 120, 000 28, 640, 000 28, 796, 000	\$1, 094, 592 1, 053, 624 1, 456, 560 2, 148, 000 2, 678, 028	\$5, 510, 440 6, 739, 467 7, 018, 812 7, 874, 886 8, 172, 609
1860-1942	<sup>2</sup> 55, 094	14, 094, 561	<sup>2</sup> 58, 127	7, 156, 614	<sup>2</sup> 90, 686	11, 575, 022	88, 284, 329

<sup>1 1860-1903:</sup> Figures not available; 1904-42: 8,387,210 tons produced.

2 Short tons.

Gold and silver produced at placer mines in Washington, 1938-42, in terms of recovered metals

	Go	ld	Silve	Matal las	
Year  1938	Fine ounces  1, 575 2, 261 2, 747 540	Value \$55, 125 79, 135 96, 145 18, 900	Fine ounces  218 358 720 90	Value \$141 243 512 64	\$55, 266 79, 378 96, 657 18, 964
1942	356	12, 460	59	42	12, 502

Gold.—The output of recoverable gold from lode and placer operations in Washington declined 10 percent in 1942 from 1941. quantity recovered from placer operations has been of minor importance compared with that from lode mines, and in 1942 placers yielded only 356 fine ounces. Several factors contributed to this decline, the more important of which were shortages of labor and supplies to maintain normal operations in gold mines and the issuance of a Government order in October 1942 which resulted in the closing or greatly curtailing of operations by several small mines. The direct result of interference with normal gold-mining operations was that much less siliceous gold ore was treated. Gold recovered by amalgamation, by cyanidation, from concentrates smelted, and from crude ore shipped direct to smelters all declined; however, gold recovered from copper concentrates smelted increased. Gold recovered in bullion from ores treated at cyanidation plants (with or without concentration equipment) declined in both Ferry and Stevens Counties; in Chelan County 940 ounces of gold came from the cyanidation of current tailings, whereas none was recovered in 1941. Gold recovered

では、 ではなるには、 ではないないできるとのできると、 できるとのできるとのできるというできるというできるというできるというできるというできるというできるというできるというできるというできるというできるというできると

THE PERSON NAMED IN

from gold concentrates made in the concentrating sections of cyanide mills in Ferry County showed a drop in 1942. Gold recovered at amalgamation mills declined in each of the counties in which such mills were operated. Gold recovered from crude ore shipped direct to smelters declined in Ferry and Okanogan Counties but increased in Chelan County. Copper concentrates produced by the Howe Sound Co. yielded 63 percent of the State total gold, and gold concentrates produced from the Knob Hill property yielded 24 percent. Other important producers of gold were the Aurum and Valley mines in Ferry County. The total output of gold ore was 93,957 tons in 1942, compared with 178,121 tons in 1941, and was treated as follows: 71,232 tons cyanided, 125 tons amalgamated, 21,150 tons shipped

crude to smelters, and 1,450 tons concentrated.

Silver.—The output of recoverable silver in Washington declined 8 percent in 1942 from 1941, and declines were noted in all the larger The largest outputs were in Chelan, Ferry, producing counties. Stevens, and Pend Oreille Counties; and mines in Chelan and Ferry produced 92 percent of the State total. Copper ore yielded 48 percent of the total silver, gold ore 45 percent, and zinc-lead ore 7 percent; the remainder came from lead ore, lead-copper ore, and placers. The Holden property of the Howe Sound Co. in Chelan County was again the largest producer of silver in the State, followed by the Knob Hill property, operated by Knob Hill Mines, Inc., in Ferry County; these two properties produced 85 percent of the State total. Other producers of silver were the Aurum and Valley properties in Ferry County; the Pend Oreille Mines & Metals Co. property in Pend Oreille County; and the Zenith Mines, Inc., and Sierra Zinc Co. properties, both in Stevens County. Placer mines yielded 59 fine ounces of silver.

Copper.—The output of recoverable copper in Washington in 1942 was 16,060,000 pounds, or less than in any year since 1938 although the tonnage of copper ore treated was greater than in any previous year. The Howe Sound Co. shipped copper concentrates rich in gold from its Holden property in Chelan County and accounted for 99 percent of the State total output of copper; the value of the recoverable gold in these concentrates was equivalent to 88 percent of the value of the Among other copper producers were the Sunset mine of the Kromona Mines Corporation in Snohomish County and the Lucky

Boy mine in Stevens County.

Lead and zinc.—The production of recoverable zinc in Washington in 1942 was the greatest in the history of the State, exceeding that of 1941 by 156,000 pounds; the production of recoverable lead was 1,896,000 pounds greater than in 1941 and only 87,687 pounds less than in the record year 1917, when 9,789,687 pounds were produced. Three properties in Pend Oreille County produced 94 percent of the State total lead and 95 percent of the zinc; virtually all the rest of the lead and zinc recovered came from two properties in Stevens County. The lead output from Pend Oreille County was greater than in 1941, but the zinc output declined; however, this decrease was more than offset by the increase from operations in Stevens County. Zinc-lead ore treated in the two flotation mills (Pend Oreille and Grandview) in Pend Oreille County exceeded that treated in 1941 by 36,585 tons; it averaged 1.50 percent in lead and 4.70 percent in zinc, compared with 1.39 percent in lead and 5.35 percent in zinc in 1941. Zinc-lead ore treated in Stevens County totaled 14,064 tons in 1942, compared with 2,051 tons in 1941; the average grade of the ore was higher than that from mines in Pend Oreille County.

# MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, copper, lead, and zinc in Washington in 1942, by counties, in terms of recovered metals

County		produc- ng	Gold (lode a	and placer)	Silver (lode and placer)		
	Lode	Placer	Fine ounces	Value	Fine ounces	Value	
Asotin Benton Chelan Douglas Ferry Grant Kittitas Okanogan Pend Oreille Snohomish Stevens Whatcom Yakima	7 - 6 5 2 - 11 3 1	8 2 2 1 1 3 3	173 104 48, 685 1 25, 256 71 3 300 36 712 55	\$6,055 3,640 1,703,975 35 883,960 2,485 10,500 1,260 24,920 1,925	28 17 174, 790 164, 987 14 457 9, 630 1, 582 17, 460 21 52	\$20 12 124, 295 117, 324 10 325 6, 848 1, 125 12, 416 15	
Total, 1941	37 61	18 56	75, 396 84, 176	2, 638, 860 2, 946, 160	369, 038 402, 030	262, 427 285, 888	

County	Cor	oper	Lea	ıd	Z	Total		
County	Pounds	Value	Pounds	Value	Pounds	Value	value	
AsotinBenton							\$6, 075	
Chelan Douglas	15, 909, 000	\$1, 924, 989					3, 652 3, 753, 259 35	
Ferry Grant	1,000	121					1, 001, 405 2, 495	
Kittitas Okanogan Pend Oreille	9, 000	1,089	600 9, 106, 000	\$40 610, 102	27, 240, 000	\$2, 533, 320	105 11, 954	
Snohomish Stevens Whatcom	99, 000 40, 000	11, 979 4, 840	595, 400	39, 892	1, 556, 000	144, 708	3, 150, 270 14, 364 226, 776	
Yakima	2,000	242					1,940 279	
Total, 1941	16, 060, 000 17, 372, 000	1, 943, 260 2, 049, 896	9, 702, 000 7, 806, 000	650, 034 444, 942	28, 796, 000 28, 640, 000	2, 678, 028 2, 148, 000	8, 172, 609 7, 874, 886	

Gold and silver produced at lode mines in Washington in 1942, by counties, in terms of recovered metals

County	Ore sold or treated (short tons)	Gold (fine ounces)	Silver (fine ounces)
Chelan Ferry Okanogan Pend Oreille. Snohomish Stevens Whatcom Yakima	716, 017 88, 123 1, 641 397, 630 1, 001 18, 398 122 5	48, 682 25, 256 300 35 712 55	174, 790 164, 987 457 9, 630 1, 582 17, 460 21 52
'Total, 1941	1, 222, 937 1, 238, 509	75, 040 83, 636	368, 979 401, 940

Gold and silver produced at placer mines in Washington in 1942, by counties, in fine ounces, in terms of recovered metals

County		Sluicing and hydraulic		Dragline and dry- land dredges <sup>1</sup>		Total		
	4,	7.82	Gold	Silver	Gold	Silver	Gold	Silver
AsotinBenton		 	27	2	146 104	26 17	173 104	28 17
Chelan Douglas		 	3 1				3 1	
Grant Kittitas Snohomish		  	3 1		71	14	、71 3 1	14
Total, 1941			35 207	2 26	321 333	57 64	356 540	59 90

<sup>&</sup>lt;sup>1</sup> A floating washing plant supplied with gravel by a dragline excavator is called a "dragline dredge"; a stationary or movable washing plant supplied with gravel by any type of power excavator is called a "dry-land dredge."

### MINING INDUSTRY

これには大学をあるないないとのないと、 とれて、

Six properties in Washington produced 1,192,927 tons of ore in 1942, or 98 percent of the State output. This ore included copper ore from the Holden mine in Chelan County; zinc-lead ore from the Pend Oreille, Metaline, and Grandview properties in Pend Oreille County and the Blue Ridge property in Stevens County; and gold ore from the Knob Hill mine in Ferry County. Development work on these six properties in 1942 included completion of 19,212 feet of drifts, crosscuts, raises, shafts, and tunnels, 71,192 feet of diamond drilling, and 434 feet of churn drilling.

#### ORE CLASSIFICATION

Details of ore classification are given in the chapter of this volume on Gold and Silver.

Ore sold or treated in Washington in 1942, with content in terms of recovered metals

Source	Mines pro- ducing	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)
Dry and siliceous gold ore	18 5 7 2 6	93, 957 717, 124 161 5 411, 690	26, 524 1 48,399 	165, 960 1 176,348 712 553 25, 406	10, 600 16, 036, 400 328 12, 672	105, 860 1, 151 9, 594, 389	28, 796, 000
Total, lode mines Total, placers	2 37 18	1, 222, 937	75, 040 356	368, 979 59	16, 060, 000	9, 702, 000	28, 796, 000
Total, 1941	55 117	1, 222, 937 1, 238, 509	75, 396 84, 176	369, 038 402, 030	16, 060, 000 17, 372, 000	9, 702, 000 7, 806, 000	28, 796, 000 28, 640, 000

Includes 940 ounces of gold and 2,557 ounces of silver from current tailings cyanided.
 A mine producing more than 1 class of ore is counted but once in arriving at total for all classes.

## METALLURGIC INDUSTRY

Lode mines in Washington produced 1,222,937 tons of ore in 1942, treated as follows: 1,130,075 tons in straight concentration mills, 71,232 tons in cyanide mills and a cyanide-concentration mill, 125 tons in amalgamation mills, and 21,505 tons shipped crude to smelters.

Amalgamation plants.—Five straight amalgamation plants and one amalgamation and concentration plant treated 125 tons of gold ore in 1942. The Morning Star mine in Ferry County was the chief

producer.

Cyanidation mills.—The cyanide plant at the Holden mill of the Howe Sound Co. operated about 8 months in 1942, during which time 180,000 tons of current tailings from copper ore were treated. The 400-ton Knob Hill cyanide-concentration mill treated gold ore from the Knob Hill mine; the plant operated throughout 1942. The First Thought 50-ton cyanide mill was operated on ores from the First Thought property until May, when the property was closed. These three plants treated 247,732 tons of ore and current tailings (180,000 tons) and reported the consumption of 307,465 pounds of calcium cyanide, 4,000 pounds of sodium cyanide (91-percent grade), 20,775 pounds of zinc dust, 1,460 pounds of lead acetate, 2,600 pounds of lead nitrate, and 856,220 pounds of lime.

Concentration mills.—A total of 1,130,075 tons of ore was treated at 11 flotation mills, as follows: 716,928 tons of copper ore at 3 mills, 411,690 tons of zinc-lead ore at 5 mills, and 1,457 tons of gold, lead, and lead-copper ores at 3 plants.

Details of the treatment of all ore produced in Washington in 1942 are given in the following tables.

Mine production of metals in Washington in 1942, by methods of recovery, in terms of recovered metals

Method of recovery	Material treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)
Ore¹ amalgamated Ore and tailings cyanided Concentrates smelted Ore smelted Placer	125 <sup>2</sup> 247, 732 71, 492 21, 505	264 3, 943 65, 422 5, 411 356	87 18, 091 323, 029 27, 772 59	15, 991, 791 68, 209	9, 595, 622 106, 378	28, 796, 000
Total, 1941		75, 396 84, 176	369, 038 402, 030	16, 060, 000 17, 372, 000	9, 702, 000 7, 806, 000	28, 796, 000 28, 640, 000

 <sup>1</sup> See footnote 1 of following table.
 2 Comprises 180,000 tons of current tailings from copper ore concentrated in Chelan County, 63,952 tons of current tailings from 67,452 tons of gold ore first treated by concentration in Ferry County, and 3,780 tons of crude ore from Stevens County

Mine production of metals from amalgamation and cyanidation mills (with or without concentration equipment) in Washington in 1942, by types of mills and by counties, in terms of recovered metals

#### AMALGAMATION MILLS

		Recovered	l in bullion	Concentrates smelted and recovered metal				
County	Ore treated (short tons)	Gold (fine ounces)	Silver (fine ounces)	Concentrates produced (short tons)	Gold (fine ounces)	Silver (fine ounces)		
Ferry	(1)	1 217	1 82					
Okanogan Whatcom	120	7 40	2 3	6	14	16		
Total, 1941	1 125 694	1 264 777	1 87 363	6 5	14 3	16		
	CY	ANIDATIO	N MILLS					
Chelan Ferry Stevens	(2) 67, 452 3, 780	2 940 2, 408 595	2 2, 557 15, 205 329	3, 500	17, 743	125, 078		
Total, 1941	71, 232 135, 290	3, 943 6, 582	18, 091 16, 996	3, 500 3, 590	17, 743 18, 969	125, 078 109, 818		

Gold and silver from amalgamation in Ferry County came from metallics (less than half a ton) from gold ore shipped crude to smelter.
 Material cyanided was 180,000 tons of current tailings from copper ore.

Mine production of metals from concentrating mills in Washington in 1942, by counties, in terms of recovered metal

	0		Concentra	ites smelte	d and recove	ered metal	
County	Ore treated (short tons)	Concen- trates pro- duced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Chelan Okanogan Pend Oreille Snohomish Stevens	715, 726 1, 450 397, 626 810 14, 463	34, 628 43 31, 323 60 1, 932	47, 424 116 8 117	172, 067 154 9, 622 75 16, 017	15, 908, 400 6, 846 36, 745 39, 800	9, 101, 058	27, 240, 000 1, 556, 000
Total, 1941	1, 130, 075 1, 063, 076	67, 986 68, 276	47, 665 46, 476	197, 935 220, 006	15, 991, 791 17, 155, 667	9, 595, 622 7, 689, 648	28, 796, 000 28, 640, 000

Gross metal content of concentrates produced from ores mined in Washington in 1942, by classes of concentrates smelted

	Concen-	Gross metal content								
Class of concentrates	trates pro- duced (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zinc (pounds)				
Dry gold	3, 515 34, 790 6, 728 1 26, 458	17, 833 47, 472 39 78	125, 200 172, 280 9, 086 117 16, 346	6, 958 16, 473, 023 2, 516 150 11, 054	9, 620, 797 470 512, 935	414, 073				
Total, 1941	71, 492 71, 871	65, 422 65, 448	323, 029 329, 832	16, 493, 701 17, 685, 859	10, 134, 202 8, 588, 909	32, 503, 154 32, 495, 120				

Mine production of metals from Washington concentrates shipped to smelters in 1942, in terms of recovered metals

#### BY COUNTIES

	Concentrates (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)	Zine (pounds)
Chelan Ferry	34, 628 3, 500	47, 424 17, 743	172, 067 125, 078	15, 908, 400		
Okanogan Pend Oreille	- 43 - 31, 323	116	154 9, 622	6,846	9, 101, 058	27, 240, 000
Snohomish Stevens Whatcom	1,932 6	8 117 14	75 16, 017 16	36, 745 39, 800	494, 564	1, 556, 000
Total, 1941	71, 492 71, 871	65, 422 65, 448	323, 029 329, 832	15, 991, 791 17, 155, 667	9, 595, 622 7, 689, 648	28, 796, 000 28, 640, 000
	BY CLAS	SES OF CO	ONCENTRA	ATES		
Dry gold	3, 515	17, 833	125, 200			
Copper Lead	34, 790 6, 728	47, 472 39	172, 280 9, 086	15, 978, 991 2, 157	9, 235, 840	
Lead-copper Zinc	26, 458	78	117 16, 346	128 10, 515	451 359, 331	28, 796, 000

65, 422

323, 029

15, 991, 791

9, 595, 622

28, 796, 000

71, 492

# GOLD, SILVER, COPPER, LEAD, AND ZINC IN WASHINGTON 511

Gross metal content of Washington crude ore shipped to smelters in 1942, by classes of ore

	Ore (short		Gross met	al content	
Class of ore	tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)
Dry and siliceous gold	21, 150 196 156 3	5, 384 27	25, 091 1, 559 686 436	4, 224 66, 656	1, 042 109, 752 874
Total, 1941	21, 505 39, 449	5, 411 10, 829	27, 772 54, 749	71, 203 226, 546	111, 668 121, 847

Mine production of metals from Washington crude ore shipped to smelters in 1942, in terms of recovered metals

### BY COUNTIES

	<u> </u>			1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	
	Ore (short tons)	Gold (fine ounces)	Silver (fine ounces)	Copper (pounds)	Lead (pounds)
Chelan Ferry Okanogan Pend Oreille Snohomish Stevens Whatcom Yakima	291 20,671 186 4 191 155 2	318 4,888 177 27	166 24,622 301 8 1,507 1,114	600 1,000 2,154 62,255 200	600 4, 942 100, 836
Total, 1941	21, 505 39, 449	5, 411 10, 829	27, 772 54, 749	2,000 68,209 216,333	106, 378 116, 352
I.	BY CLASSES	OF ORE			
Dry and siliceous gold	21, 150 196 156 3	5, 384 27	25, 091 1, 559 686 436	3, 754 64, 255 200	600 105, 078 700
	21, 505	5, 411	27,772	68, 209	106, 378

### REVIEW BY COUNTIES AND DISTRICTS

Mine production of gold, silver, copper, lead, and zinc in Washington in 1942, by counties and districts, in terms of recovered metals

County and district	di	ines ro- uc- ng	Ore sold or treated	Go (fir ound	1e	Silve (fin ounce	e	Copper	Lead	Zine	Total
	Lode	Placer	(short tons)	Lode	Placer	Lode	Placer	(pounds)	(pounds)	(pounds)	value
Asotin County:											
Snake River		8			173		28			l	\$6,075
Benton County:			1.138 (1) 3					1444 20 674		4.0	1
Columbia River	L	2			104		17				3, 652
Chelan County:					100						1000
Chelan Lake	1		715, 726	48, 364		174, 624		15, 908, 400 600		l	3, 741, 833
Peshastin Creek	Ī	1	291	318	1	166		600	l		11, 356
Wenatchee River		l ī	5		2						70
Douglas County:		-			100						
Columbia River	1	1			1						35
Ferry County:		1 -	7.5		100						
Danville	1	1	124	275		128		1,000			9, 837
Republic	6					164, 859		_, _,			991, 568
Grant County:	ľ		0.,500	, 001		101,000		1.4	4. 100		1 201,000
Columbia River	40.60	1 1		100	71		14				2, 495
Kittitas County:		-	7575		1						
Swauk		9			2						70
Yakima River		1			ĩ		7.77				35
Okanogan County:	777	-			1						
Cascade	1		58	63	2.00	128	7 .				2, 296
Conconully	i		5	1		120					35
Methow	3		1, 554	212		263		0.000			8, 696
Myers Creek and	۰		1,001	212		200		0,000			0,000
Mary Ann Creek	1		24	24		66			600		927
Pend Oreille County:	- 1			21					000		821
Metaline	5		397, 630	100	1 7 5	9, 630			0 106 000	27, 240, 000	2 150 970
Snohomish County:	٥		381,000			9,000			8, 100, 000	21, 240, 000	0, 100, 210
Index	1		938	21		1, 381		05 000			13, 309
Sultan	i		63	14	ī	201		90,000			
Stevens County:	-	-	00	1.2	1	201		3, 200			1,055
Bossburg	1	a	100	100	- 41	585			52, 600		3, 940
Deer Trail			1, 859			8, 145		1,700	167 200	186,000	34, 750
Kettle Falls	1		1,009			436		200	700	100,000	381
Northport			12, 264	110					274 900	1, 370, 000	100 015
	. 0			595		7,875		11, 100			
Orient Springdale	1		3, 780 392	090		329 90		07.000			21, 059 3, 331
Whatcom County:			592			. 90		21,000			0, 001
Mount Baker			60	32	١.						1 100
	1			32 23							1, 120
Slate Creek	2		62	23		21					820
Yakima County:	4							0.000	7 1 1		C=0
Bumping Lake	. 1		5			52		2,000			279
Total Washington.	37	18	1, 222, 937	75, 040	356	368, 979	59	16, 060, 000	9, 702, 000	28, 796, 000	8, 172, 609

### ASOTIN COUNTY

Most of the gold output from Asotin County in 1942 came from the operations of three small dragline dredges on Snake River. All placer operations employing mechanical equipment closed in October 1942.

### BENTON COUNTY

All the gold output from Benton County in 1942 came from two dry-land dredges operating on Columbia River.

THE RESERVE OF THE PARTY OF THE

#### CHELAN COUNTY

Chelan Lake district.—The Holden mine of the Howe Sound Co. continued to be the leading producer in 1942 of gold, silver, and copper in Washington. The company treated 715,726 tons of copperzinc ore, which averaged 0.083 ounce of gold and 0.308 ounce of silver to the ton, 1.21 percent copper, and 1.02 percent zinc. The quantity of ore treated was 28,383 tons greater than in 1941 but of lower copper content; as a consequence, the copper output of the State declined. The company long has been treating large tonnages of ore of about equal zinc and copper content, but it was not until 1942 that steps were taken to recover the zinc. In 1942 equipment was added to the mill whereby zinc concentrates as well as copper concentrates were to be recovered, but actual recovery of zinc concentrates did not begin until late in December of that year. The rated milling capacity of the 2,000-ton concentrator was not increased in 1942, although an average of 2,101 tons of ore a day was treated compared with 2,056 tons in 1941. The cyanide plant, added to the concentrator late in 1941, treated current tailings from the copper ore until September 6, 1942, when it was closed. During the operating period 180,000 tons of current tailings were treated and resulted in the recovery of 940 ounces of gold and 2,557 ounces of silver. Development work in 1942 included sinking 347 feet of vertical shaft, driving 8,031 feet of drifts, and 2,862 feet of raises, besides completing 19,507 feet of diamond drilling. The total footage of development work done in 1942 was equivalent to about half that completed in 1941.

Peshastin Creek district.—Gold ore shipped crude to the Tacoma smelter from the Polepick mine was the only production in the

Peshastin Creek district in 1942.

### FERRY COUNTY

Danville district.—The Morning Star Mining Co. operated its gold property in 1942 from January to May and in December and produced about half the quantity of metals produced in 1941. The intervening

period was spent in developing an adjoining copper property.

Republic district.—Siliceous ore, from which the entire metal output of the Republic district was recovered, amounted to 87,999 tons in 1942 and comprised 67,452 tons cyanided and 20,547 tons shipped direct to smelters. Knob Hill Mines, Inc., was again the chief producer in the district but treated ore from the Knob Hill mine only; it handled 67,452 tons of gold ore in its 400-ton flotation-cyanidation mill, producing 3,500 tons of gold concentrates in addition to cyanide The company announced that development work in 1942 included 2,459 feet of diamond drilling and 434 feet of churn drilling; also, that all open-cut mining was discontinued.

The Aurum Mining Co. operated the Aurum group throughout 1942 and continued to supply most of the crude ore shipped direct to smelter from the Republic district. The Valley mine produced about 5,800 tons of highly siliceous gold ore, which was shipped direct to the Tacoma smelter. Other producers of gold ore shipped direct to smelters included the Republic group, operated by the Eureka Mining & Milling Co., and the South Penn property.

#### GRANT COUNTY

A dragline dredge operated by Miller Bros. at Chinaman Bar on Columbia River accounted for all the gold recovered in Grant County in 1942.

### KITTITAS COUNTY

Some placer gold was recovered from sluicing and hydraulic operations in 1942 from gravels in the Swauk and Yakima River districts.

### OKANOGAN COUNTY

Cascade district.—Metal from crude gold ore shipped direct to the Tacoma smelter from the Bodie group near Wauconda comprised the

output from the Cascade district in 1942.

Methow district.—The Methow M & M Co. treated gold ore in a small concentrating mill in 1942 and was the largest producer in the Methow district. Other producers were the Highland Light & Hidden Treasure, Alder group, and Crystal Mountain group of properties.

PEND OREILLE COUNTY

Metaline district.—Most of the recovered lead and zinc from Washington in 1942 was derived from the zinc-lead ores of the Metaline The value of the recovered metals increased from \$2,573,300 in 1941 to \$3,150,270 in 1942 as the result of an increased output of lead and a higher unit price for lead and zinc. The Pend Oreille Mines & Metals Co., chief producer in the district, operated its Josephine group of properties throughout the year and treated an average of 642 tons (based on a 365-day year) of zinc-lead ore per day in its 700-ton flotation mill. The average grade of the ore treated in 1942 was 1.66 percent lead and 4.28 percent zinc, compared with 1.11 percent lead and 4.84 percent zinc in 1941. The lead concentrates produced averaged about 78 percent, and the zinc concentrates averaged 62 percent. Mine development, according to the company report, amounted to about 18,000 feet of diamond drilling and the driving in aggregate of about 2,700 feet of tunnel, raises, and shafts. The company also reported the opening of the 1,000-foot and 1,500foot levels. Most of the remainder of the lead output of the district and all the zinc were contained in the high-grade lead and zinc concentrates produced at the Grandview mill of the American Zinc, Lead & Smelting Co. The capacity of this mill, which treats zinc-lead ore from the properties of the American Zinc, Lead & Smelting Co. and the Metaline Mining & Leasing Co., was increased from 450-500 tons a day to 600 tons by adding classifying capacity in 1942. Grandview mill treated about 22,000 tons of ore more than was treated in 1941, but the average lead and zinc content of the mill ore was lower. The American Zinc, Lead & Smelting Co. reported that mine development comprised completion of 12,028 feet of diamond drilling and 1,512 feet of drifts. The Metaline Mining & Leasing Co. reported that development comprised completion of 19,131 feet of diamond drilling, 3,058 feet of drifts, and 130 feet of shaft. Other production in the district included lead ore shipped crude to a smelter from the Cliff and Velvet Lode properties.

#### SNOHOMISH COUNTY

Index district.—The Kromona Mines Corporation, only active producer in the Index district in 1942, shipped crude copper ore direct to a smelter and also produced some copper concentrates. company output was substantially lower than in 1941.

Sultan district.—Some copper ore was shipped crude to a smelter from the property of the Pacific Nickel Co. A little placer gold was

recovered from sluicing along Sultan River.

### STEVENS COUNTY

Bossburg district.—The Bonanza mine, an old property near Evans, was reopened by Russell Parker in June; equipment was installed, and operations were begun the latter part of the month. During the remainder of the year the property produced 100 tons of lead ore, containing 585 ounces of silver and 54,994 pounds of lead. A 60-ton concentration mill is to be installed early in 1943.

Deer Trail district.—Zenith Mines, Inc., operated the Cleveland mine during 1942 and treated 1,859 tons of zinc-lead ore in a small The ore treated averaged about 6 percent lead and flotation mill.

7 percent zinc.

Kettle Falls district.—A small lot of lead-copper ore was shipped

crude to a smelter from the Silver Queen mine.

Northport district.—The Sierra Zinc Co. operated throughout 1942 its 60-ton flotation mill, built late in 1941. A total of 12,123 tons of zinc-lead ore was milled, which contained about 0.01 ounce of gold and 0.6 ounce of silver to the ton, 1.59 percent lead, and 7.36 percent zinc. The mill was operated continuously except for short periods during the winter months; these temporary shut-downs were caused for the most part by weather conditions. Minor additions were made to the mill in 1942, and some adjoining property was acquired for a tailings pond and to furnish a sufficient supply of mine timber. A 40-ton flotation mill was constructed in 1942 on the property of the Frisco Standard Machinery was installed, and a test run was made Co. near Ione. on the lead-copper ore. The property was closed late in October after the tests were completed; operations are to be resumed in the spring of 1943. Among other producers in the Northport district in 1942 were the Electric Point, Gladstone Mountain, and Van Stone, all of which shipped crude lead ore direct to a smelter.

Orient district.—The only producer in the Orient district in 1942 was the First Thought Mine Corporation, which treated 3,780 tons of gold ore in its 50-ton cyanide mill. In May, operations were

suspended for the duration of the war.

Springdale district.—Operations at the Lucky Boy mine began in June and continued throughout the rest of 1942. During this period, 392 tons of copper ore were treated in the Deer Trail 100-ton flotation mill.

# WHATCOM COUNTY

Mount Baker district.—Gold ore from the Boundary Red Mountain mine, treated by amalgamation, comprised the output of the Mount Baker district in 1942.

Slate Creek district.—A little gold ore from the property of the Slate Creek Mining Co. was treated by amalgamation and concentration and a sample lot of ore from the Mammoth group was shipped crude to a smelter.

### YAKIMA COUNTY

Bumping Lake district.—Some old clean-up of copper ore and mill cleanings was shipped direct to a smelter in 1942 from the property of the Copper Mining Co.

# GOLD. SILVER. COPPER. AND LEAD IN WYOMING

(MINE REPORT)

By Chas. W. HENDERSON

### SUMMARY OUTLINE

			Page	★ これが、ため、これは、自動作品のは作品をよる。	Page
Summary			_ 517	Mine production by counties	518
Calcula	tion of value o	of metal production	- 517	Review by counties and districts	

#### STIMMARY

Lode and placer mines in Wyoming in 1942 vielded—in terms of recovered metals—23 fine ounces of gold, 52 fine ounces of silver, and 6,000 pounds of lead; the total calculated value was \$1,244. Of the total metal produced, 12 ounces of gold were recovered from placer mining—the output from six properties in the Atlantic City district.

Fremont County.

No large lode-mining operations were carried on in the State to recover gold, silver, copper, or lead in 1942. Six small lode mines, none of which shipped or treated over 25 tons of crude ore, yielded in terms of recovered metals—11 fine ounces of gold, 52 fine ounces of silver, and 6,000 pounds of lead. Lead ore totaling 25 tons (yielding the bulk of the silver and all the recovered lead produced in the State in 1942) was shipped from the Black Buttes claim in Crook County to the Garfield (Utah) smelter. A total of 59 tons of crude ore was treated in five small amalgamation mills—four in Fremont County and one in Johnson County—which recovered 11 ounces of gold and 1 ounce of silver.

All tonnage figures are short tons and "dry weight"; that is, they

do not include moisture.

The value of the metal production herein reported has been calculated at the following prices.

### Prices of gold, silver, copper, lead, and zinc, 1938-42

1.	Year	Gold 1	Silver 3	Copper 3	Lead 4	Zine 4
1938 1939 1940 1941		Per fine ounce \$35.00 35.00 35.00 35.00 35.00	Per fine ounce \$ \$0. 646+ \$ 6.678+ \$ 7.711+ \$ 7.711+	Per pound \$0.098 . 104 . 113 . 118	Per pound \$0.046 .047 .050 .057	Per pound \$0.048 .055 .063 .078

¹ Price under authority of Gold Reserve Act of January 31, 1934. Treasury legal coinage value of gold from January 18, 1837, to January 31, 1934, was \$20.67+(\$20.671835) per fine ounce.

¹ Treasury buying price for newly mined silver.

¹ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production but excludes value of foreign copper delivered to Metals Reserve Co. for domestic consumption.

¹ 1938-41: Yearly average weighted price of all grades of primary metal sold by producers; 1942: Price includes bonus payments by Metals Reserve Co. for over-quota production.

¹ \$0.64646464.

¹ \$0.67878787.

¹ \$0.71111111.

The following table shows the annual output of ore from lode mines producing gold, silver, copper, and lead and the quantity and value of the metals recovered from both lode and placer mines in Wyoming from 1938 to 1942; it also gives the total production of metals from 1867 to 1942. About three-fourths of the total recorded value of the four metals is in copper, most of which was mined before 1924 in the Encampment district, in Carbon County, and the Hartville district, originally in Laramie County, now in Platte County.

Mine production of gold, silver, copper, and lead in Wyoming, 1938-42, and total, 1867-1942, in terms of recovered metals

Year	Ore (short		(lode and acer)	Silver (lode and placer)		Copper		Le	ad	Total
i ear	tons)	Fine ounces	Value	Fine ounces	Value	Pounds	Value	Pounds	Value	value
1938 1939.	581 57	798 583	\$27,930	328	\$212	1.000				\$28, 142
1940 1941 1942	813 159 84	740 478 23	20, 405 25, 900 16, 730 805	75 114 94 52	51 81 67 37	4, 000 8, 000	\$452 944	6,000	\$402	20, 456 26, 433 17, 741 1, 244
1867-1942	(1)	77, 914	1, 835, 318	74, 632	51, 752	<sup>2</sup> 16, 325	5, 684, 048	2 11		7, 572, 088

<sup>&</sup>lt;sup>1</sup> Figures not available.

### MINE PRODUCTION BY COUNTIES

Mine production of gold, silver, and lead in Wyoming in 1942, by counties, in terms of recovered metals

County		ines ucing	Ore sold or		Gold			Silver				Total
County	Lode	Plac- er	treat- ed	Lode	Placer	Total	Lode	Placer	Total	Copper	Lead	value
Crook Fremont Johnson	1 4 1	6	Short tons 25 44 15	Fine ounces	Fine ounces	Fine ounces	Fine ounces 51	Fine ounces	Fine ounces 51	Pounds	Pounds 6, 000	\$438 771 35
Total, 1941	6 8	6 12	84 159	11 31	12 447	23 478	52 44	50	52 94	8,000	6, 000	1, 244 17, 741

# REVIEW BY COUNTIES AND DISTRICTS

#### ALBANY COUNTY

Douglas Creek district.—Development and assessment work were the only mining operations carried on in Albany County during 1942. Ira J. Knisley, of Holmes, did assessment work on the Depression No. 1 and 2 placer ground on the west branch of Little Beaver Creek. The Independence Gold Mining Co., Inc., did development work and made tests for the treatment of ore from its Independence group of claims 3½ miles west of Centennial.

# CARBON COUNTY

Encampment or Upper Platte district.—Development and assessment work were done on the Golden Clover claim, 15 miles south of Encampment, by the Golden Clover Mining Co.

<sup>3</sup> Short tons.

#### CROOK COUNTY

Hurricane district.—One car of lead ore containing 51 ounces of silver and 6,977 pounds of lead was shipped to the East Helena (Mont.) plant from the Black Buttes claim south of Sundance by L. Two types of ore were mined—a lead F. Fletcher of Moorcroft. carbonate ore and a sulfide ore.

### FREMONT COUNTY

Atlantic City district.—Placer mining in the Atlantic City district in 1942 yielded 12 ounces of gold valued at \$420. Frank Antich, Atlantic City, operated the Miners Delight placer and treated about 2,400 cubic yards of gravel, from which 7.38 ounces of gold were recovered; the average fineness of the bullion was 0.851 in gold. was the largest single producer of gold in the State in 1942. No other individual placer operation in the Atlantic City district produced more than 2 fine ounces of gold. Six hundred cubic yards of gravel from the Bonanza placer, yielding 1.52 ounces of gold, were treated by R. A. Swabes of Rock Springs. Joe Barbett, operating the Timba-Bah Mining Co. property about 5 miles below Atlantic City (largest single producer of gold and silver in the State in 1941), produced 1.67 ounces of gold. Individuals sluicing at the Badger-Fox-Coyote, Big Atlantic, and Sweetwater River placers near Atlantic City and South Pass City recovered small lots of placer gold, which were sold to the Smith-Sherlock Co. at South Pass City.

Roy A. Cowden, of Atlantic City, operated the Gold Leaf and Mint lode-mining claims and treated 24 tons of ore in a 5-ton Gibson amalgamation mill, producing 5½ ounces of gold bullion, which was sold to the Denver Mint. James Cassie did development and assessment work on the Reynolds group of claims southeast of Atlantic City and treated about 20 tons of ore, producing 3½ ounces of gold bullion, which was sold to the Denver Mint. Some development work, consisting of 100 feet of tunnel, was done at the McGrath-Diana mine; the mill equipment and buildings were sold and moved

to Ten Sleep, Washakie County, during the summer of 1942.

Copper Mountain district.—Charles Simerson operated the Gold Nugget mine on Copper Mountain; about 3 ounces of gold were produced.

#### GOSHEN COUNTY

Some development work was done on the old Michigan mine in the Hartville Uplift region, northeast of Sunrise, by Oscar Alexander, of Manville. No shipments were made.

### JOHNSON COUNTY

The Powder River Exploration Syndicate treated a few tons of ore from the Powder River mine and shipped 5 ounces of gold bullion to the Denver Mint. The property is in the Big Horn Mountains southwest of Buffalo and was recently purchased by the Empire State Oil Co. of Thermopolis.

#### PARK COUNTY

No metal was produced from Park County in 1942. Charles F. Wolf and associates did some sampling and exploration work on the mining claims in the Kerwin camp, about 50 miles south of Cody.

### PLATTE COUNTY

The only mining operations in Platte County in 1942 were those carried on by the Colorado Fuel & Iron Co. at its Sunrise iron mine. No copper ore was produced.

# SECONDARY METALS—NONFERROUS

By F. H. WRIGHT 1

#### SUMMARY OUTLINE

	Page		Page
General summary	521	Secondary nickel	531
Salient statistics	521	Secondary lead	533
Scope of report	522	Secondary tin	536
Secondary aluminum	522		538
Secondary magnesium	525	Secondary antimony	539
Secondary copper and brass	526	Secondary zinc	540

### GENERAL SUMMARY

Although the nonferrous secondary metals industry was handicapped by a shortage of manpower and by necessary Government restrictions on uses of certain metals, the year 1942 saw several production records broken. The value of the more important nonferrous metals recovered from scrap as unalloyed metal and in alloys and chemicals totaled \$425,991,475, compared with \$348,377,389 in 1941. Secondary metals recovered from new or byproduct scrap that left the plant of its origin were valued at \$229,126,659, and metals reclaimed from old scrap materials were worth \$196,864,816.

Salient statistics of nonferrous secondary metals recovered in the United States, 1941-42

Antimony 57 15,900 21,572 6,040,160 21,622 Copper 313,697 74,032,492 412,699 97,396,964 726,396 Lead. 17,136 1,953,504 380,280 43,351,920 397,416 Magnesium 1,737 833,760 15 7,200 1,752 Nickel. 3,181 2,226,700 2,134 1,403,800 5,316 Tin 12,427 12,926,565 29,606 30,796,161 42,033 Zine 202,813 30,421,950 81,154 12,173,100 283,967		Ne	w scrap	Old	d scrap	Total		
Aluminum         63, 744         \$20, 704, 051         43, 113         \$14, 003, 102         106, 857           Antimony         15, 960         21, 572         6, 040, 160         21, 622         6, 040, 160         21, 689         97, 386, 964         728, 386         380, 280         43, 351, 920         307, 416           Magnesium         1, 73         1, 953, 504         380, 280         43, 351, 920         307, 416           Nickel         3, 181         2, 226, 700         2, 134         1, 493, 800         5, 315           Tin         12, 427         12, 926, 565         29, 606         30, 796, 161         42, 033           Zinc         202, 813         30, 421, 950         81, 154         12, 173, 100         283, 967           1942         143, 114, 982         205, 262, 407	Metal		Value		Value		Value	
1942	Aluminum Antimony Copper Lead Magnesium Nickel	313, 697 17, 136 1, 737 3, 181 12, 427	15, 960 74, 032, 492 1, 953, 504 833, 760 2, 226, 700 12, 926, 565	21, 572 412, 699 380, 280 15 2, 134 29, 606	6, 040, 160 97, 396, 964 43, 351, 920 7, 200 1, 493, 800 30, 796, 161	106, 857 21, 629 726, 396 397, 416 1, 752 5, 315 42, 033 283, 967	\$34, 707, 153 6, 056, 120 171, 429, 456 45, 305, 424 840, 960 3, 720, 500 43, 722, 726 42, 595, 050	
1942 1E4 021 4E 070 E0E 49 661 10 766 476 100 400	1040		143, 114, 982		205, 262, 407		348, 377, 389	
Antimony         3         934         18, 197         5, 662, 906         18, 200           Copper         500, 633         118, 149, 888         427, 122         100, 800, 792         927, 755           Lead         14, 413         1, 816, 038         308, 888         38, 882, 088         233, 001           Magnesium         6, 151         2, 755, 648         87         38, 976         6, 236           Nickel         2, 2430         1, 701, 000         1, 712         1, 198, 400         4, 142           Tin         14, 057         14, 619, 280         23, 861         24, 815, 440         37, 918	Aluminum Antimony. Copper Lead Magnesium Nickel	500, 633 14, 413 6, 151 2, 430 14, 057	118, 149, 388 1, 816, 038 2, 755, 648 1, 701, 000 14, 619, 280	427, 122 308, 588 87 1, 712 23, 861	100, 800, 792 38, 882, 088 38, 976 1, 198, 400 24, 815, 440	198, 492 18, 200 927, 755 323, 001 6, 238 4, 142 37, 918 330, 526	58, 039, 061 5, 663, 840 218, 950, 180 40, 698, 126 2, 794, 624 2, 899, 400 39, 434, 720 57, 511, 524	

Recovery of secondary lead, tin, antimony, and nickel (nonferrous) declined, but reclamation of secondary aluminum, copper, zinc, and magnesium broke all previous records owing to the increased volume of fabricators' scrap that flowed from war plants. The scrap-remelting facilities of primary aluminum producers and brass mills were so

 $<sup>^{\</sup>rm I}$  Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

overtaxed that part of the furnace capacity of a number of secondary smelters and refiners was brought into use to melt wrought alloy scrap. Production of secondary brass and aluminum casting alloy ingots was greater than ever before, but unusually large quantities of refined copper, tin, and zinc were required by brass-ingot makers in addition to the scrap used for production of lead-free bronze to meet rigid specifications of the Army and Navy.

### SCOPE OF REPORT

The regular annual survey of nonferrous-scrap consumption and secondary-metal production was augmented in 1942 by a monthly canvass of approximately 4,500 scrap-metal dealers, and by separate monthly canvasses of consumers of zinc scrap and white-metal scrap. Annual reports of scrap use were received from 373 plants classed as secondary remelters, smelters, or refiners of one or more nonferrous metals, from 37 brass mills, 27 aluminum rolling mills and fabricators, 48 chemical works, and 1,219 foundries and other manufacturers that consumed purchased nonferrous scrap.

### SECONDARY ALUMINUM

The secondary-aluminum industry operated its scrap-melting facilities more nearly at capacity levels in 1942 than in 1941. The quantity of secondary aluminum 2 recovered from scrap (198,492 short tons valued at \$58,039,061) was almost double the 1941 output (106,857 short tons valued at \$34,707,153). The value was computed at 14.62 cents a pound of aluminum recovered, compared with 16.24 cents a pound in 1941. Production of primary aluminum was 521,106 short tons, and the net total production in the United States consisted of primary production plus recovery from old scrap, or 564,767 tons.

Of the 14,104 tons of secondary aluminum recovered as unalloyed metal, 21 percent appeared on the market as "pure" (98.5 percent) aluminum ingot, 6 percent as aluminum powder, and 73 percent in commercial shapes produced by rolling mills.

Secondary aluminum 1 recovered in the United States, 1941-42, in short tons

Secondary aluminum recovered			Recoverable aluminum-alloy content of scrap				
Form of recovery	1941	1942	Kind of scrap processed	1941	1942		
As metal	8, 308 2 96, 571 334 709 935 106, 857	14, 104 180, 979 1, 268 473 1, 668 198, 492	New scrap: Aluminum-base 3 Copper-base Zinc-base Old scrap: Aluminum-base 4 Copper-base Zinc-base	63, 726 12 6 63, 744 43, 049 31 33 43, 113	154, 436 297 98 154, 831 43, 249 213 199 43, 661		

<sup>&</sup>lt;sup>1</sup> In accordance with common usage, the term "aluminum" covers aluminum alloys, and the figures include all constituents of the alloys recovered from aluminum-base scrap.

<sup>Revised.
Aluminum content of new aluminum-base scrap was 59,097 tons in 1941 and 143,633 tons in 1942.
Aluminum content of old aluminum-base scrap was 39,858 tons in 1941 and 41,221 tons in 1942.</sup> 

<sup>&</sup>lt;sup>2</sup> The term "secondary aluminum" is used broadly to cover aluminum and aluminum alloys, including the weight of alloy constituents, such as copper, silicon, magnesium, and others,

By far the largest proportion of secondary aluminum (180,979 tons) was recovered in aluminum alloys in the form of ingots, wrought products, and castings. The gross weight of secondary aluminum ingots produced by aluminum smelters was 144,694 short tons, of which 138,741 tons represented alloyed aluminum recovered from scrap, and the remainder represented additions of other raw materials. Secondary aluminum-ingot production represented a 72-percent gain over 1941. Increased steel production and denial of primary aluminum for deoxidation caused production of secondary aluminum steel-mill ingot and shot to increase 59 percent and provided an outlet for secondary aluminum of high iron content.

The extensive use of rolled products for airplanes together with the Government order that made it mandatory for fabricators to sell their segregated 17S, 24S, and 52S alloy scrap in solid form to the Aluminum Co. of America or Reynolds Metals Co. resulted in greater consumption of scrap at the aluminum rolling mills. These plants of primary producers recovered 53,080 tons of aluminum alloys by combining scrap and secondary "process" ingots with primary metals used

for wrought products.

After aluminum scrap had been placed under strict control on January 7, 1942, only authorized remelters, smelters, and chemical works were allowed to consume it. Manufacturers and foundries produced only 848 tons of aluminum powder and 480 tons of aluminum alloy castings from scrap, mostly in the first week in January, and thereafter resold 680 tons of the purchased aluminum scrap they had on hand and reported only 205 short tons in inventory at the end of 1942.

In addition to these aluminum-base products, 686 tons of aluminum from aluminum scrap and 582 tons from aluminum bronze scrap were recovered in aluminum and manganese bronze products, and recovery of 176 tons of aluminum from aluminum scrap and 297 tons of aluminum from zinc-base alloy scrap was reported in zinc-base alloy

products.

Consumption of 217,611 short tons (gross weight) of purchased aluminum scrap represented an increase of 72 percent over 1941. Approximately 73 percent of the scrap was used by 75 remelters, smelters, and refiners, 26 percent by 27 plants classed as aluminum rolling mills, and 1 percent by 281 foundries and miscellaneous manufacturers. The high rate of activity in fabrication of wrought aluminum for aircraft was reflected in the fact that 80 percent of the scrap consumed in 1942 was new scrap, compared with 64 percent in 1941 and only 43 percent in 1940. The consumption of old aluminum scrap continued on a slight downward trend in 1942, having dropped from 47,572 tons in 1940 to 45,329 tons in 1941 and to 43,248 tons in 1942.

Consumption of purchased aluminum scrap in the United States in 1942, gross weight, in short tons

			Man				
Scrap item	Remelter ers, and	rs, smelt- refiners	Aluminum roll- ing mills		Foundries and other manufacturers		Total scrap used
	New scrap	Old scrap	New scrap	Old scrap	New scrap	Old scrap	
Pure clippings, wire, and foil	3, 683 2, 934 14, 697 1, 284 77, 022	704 25, 556 3, 698 11, 148	4, 658 405 44, 079 6, 462 7 10	2 17	73 35 6 10 894 19	139 350 6 36	9, 259 29, 297 62, 486 18, 940 77, 923 39
Miscellaneous aluminum and dross	17, 863	1, 584			220		19, 667
	117, 485	42, 696	55, 621	19	1, 257	533	217, 611

Dealers in nonferrous scrap metal shipped 100,796 short tons of aluminum scrap to consumers out of the 103,856 tons they collected from domestic and industrial sources during 1942. A general upward trend was noted in the monthly volume of dealers' transactions in aluminum scrap during the last 8 months of 1942 after revisions in Government regulations allowed scrap generators to sell segregated plant scrap to dealers in lots up to 5,000 pounds per month compared with the earlier limitation of 1,000 pounds. Dealers' stocks increased from 5,660 tons on hand January 1 to 8,720 tons December 31, 1942.

Consumers' stocks of purchased aluminum-base scrap in the United States at end of year, 1941-42, gross weight, in short tons

Scrap item	On hand—			
встар иеш	Dec. 31, 1941	Dec. 31, 1942		
Castings and forgings	2, 004	1, 690		
Sheet, turnings, clippings, etc	6, 070 1, 521	5, 020 1, 915		
	9, 595	8, 625		

The aluminum industry continued under close Government control throughout 1942. The overwhelming demands of a nation at war for the available supply of aluminum required further restrictive and conservation orders to supplement or replace those already operating at the beginning of 1942. On January 26, 1942, aluminum was limited to 15 uses, most of them restricted to low-grade secondary aluminum containing more than 4 percent copper and either iron or zinc in excess of 1 percent. Aluminum was limited to 2 percent in zinc-base alloys and to a maximum of 15 percent in other alloys on August 18, 1942, but an amendment on November 20 removed all restrictions on the aluminum content of zinc-base alloys. Segregation of aluminum scrap by alloy content and form was made mandatory early in 1942. Every plant generating 1,000 pounds or more of aluminum scrap per month was ordered to segregate scrap at the machine at which it was generated.

Formal Government price ceilings established in 1941 were continued throughout 1942. The basing point of aluminum scrap prices was that of No. 1 virgin aluminum ingot, which remained at 15.00 cents a pound delivered. The average selling price of 98 percent pure secondary ingot was also 15 cents. The aluminum price schedule was broadened on August 20 to cover all secondary aluminum ingot and virtually all grades of aluminum scrap. Effective October 16, 1942, an amendment established a maximum price of 1.25 cents a pound for aluminum drosses, skimmings, grindings, etc., containing less than 15 percent by weight of metallic aluminum. Later in the year, toll agreements were exempted from scrap ceilings, and premiums were allowed on briquetted scrap and material properly prepared for briquetting.

Dealers' buying prices for cast aluminum scrap in New York averaged 8.62 cents a pound, compared with 10.76 cents in 1941. The monthly average price dropped from 9.37 cents in December 1941 to 8.73 cents in January 1942, then remained static until October 1942, when the price began to decline to the year-end level of 8.12 cents a

pound.

Dealers' buying prices for new aluminum clippings in New York averaged 9.50 cents a pound, compared with 13.00 cents in 1941. The Government order in January requiring the segregation of fabricators' scrap spurred the price of new clippings from an average of 9.59 cents in January 1942 to 9.87 cents in March. Strong smelter demand for this type of graded scrap maintained the high price level through June, but the average price declined to 9.12 cents in September, where it remained for the rest of 1942.

Imports of aluminum scrap totaled 487 short tons, compared with 55 tons in 1941, and exports amounted to only 32 tons, compared with

57 tons in 1941.

# SECONDARY MAGNESIUM

Expanded production of magnesium for war uses brought a proportionate increase in the generation of magnesium scrap, and recovery of secondary magnesium from purchased scrap totaled 6,238 short tons valued at \$2,794,624, compared with 1,752 tons valued at \$840,960 in 1941. The value was computed from the average selling price of all grades of primary magnesium, which was 22.4 cents a pound in 1942 and 24 cents in 1941. Most of the secondary magnesium was recovered in the form of magnesium alloy ingot for subsequent blending with primary magnesium or alloying with aluminum, but small quantities of magnesium scrap were consumed directly in production of aluminum, lead, and zinc alloys, for deoxidation of metals, and as a chemical catalyst in the Grignard reaction.

All but 1 percent of all the secondary magnesium was reclaimed from new scrap generated in manufacturing operations, as not enough magnesium had been used in former years to build up a backlog of obsolete magnesium objects for salvage. Purchased magnesium scrap was consumed in 39 plants representing 27 companies, but 97 percent of the secondary magnesium was recovered in 10 plants of 7 companies. Consumption of magnesium scrap totaled 7,317 short tons, compared

with 2,279 tons treated in 1941.

Secondary magnesium recovered in the United States, 1941-42, in short tons

Type of product or use	1941	1942
Magnesium alloy ingot¹ (gross weight) Magnesium alloy castings (gross weight) In aluminum alloys In lead alloys In zine alloys.	929 738 60 (2) (2)	6, 045 93 46 2
Consumed in chemical and metallurgical processes  From new scrap From old scrap	1,752 1,737 1,737	6, 238 6, 151 87

<sup>&</sup>lt;sup>1</sup> Includes secondary magnesium incorporated in primary magnesium ingot.

Use of magnesium, including scrap, was closely controlled by means of priorities issued to approved users according to Federal regulations in effect February 25, 1942. Magnesium scrap could be sold only to primary producers or to seven approved secondary smelters, unless otherwise authorized, but 1,877 tons of magnesium scrap found its way into scrap dealers' yards in 1942. Some of this scrap was purchased by dealers in the belief that it was aluminum, indicating that the trade had not yet become familiar with magnesium as a metal.

Although segregation of magnesium scrap from other metals was required during 1942, it was not until December 31, 1942, that the regulations were amended to require complete segregation of magnesium scrap according to types of alloy at the scrap source.

Stocks and consumption of magnesium scrap in the United States in 1942, gross weight, in short tons

	On hand—		Consumption
	Dec. 31, 1941	Dec. 31, 1942	during 1942
Cast scrap.	15	9	223
Solid wrought scrap	22 202	8 215	126 6, 968
	239	232	7, 317

Primary magnesium ingot was quoted at 27 cents a pound at the beginning of 1942, but at the request of the Office of Price Administration producers cut the price early in February to 22.5 cents a pound, and this level was maintained for the remainder of the year. Prices of magnesium scrap and remelt ingot were covered by the General Maximum Price Regulation issued April 28, 1942, which established the ceiling price for each seller at the highest price charged during March 1942. Quotations of these prices were not available for record. Definite prices for magnesium scrap and secondary ingot were not fixed until January 20, 1943. On this date maximum prices were set at 9 cents a pound for segregated borings and turnings, 8 cents for contaminated turnings, and 21.5 cents a pound for Class A remelt magnesium ingot (A. S. T. M. specification B93-41T). Segregated plant scrap solids were exempt from the maximum price regulations.

### SECONDARY COPPER AND BRASS

Copper recovered as unalloyed metal and in brass or other alloys reclaimed from purchased <sup>3</sup> scrap totaled 927,755 short tons valued at \$218,950,180, compared with 726,396 short tons valued at \$171,429,456

The term "purchased scrap" includes scrap worked on toll for another and scrap transferred between plants owned by a single company, but does not include "home" scrap reused in the plant in which it originated.

こうこうかん かいかん かんかん 一番をひかる かいし かんかんかん

in 1941. The value was computed at 11.8 cents a pound in both years. Copper recovered as a constituent of scrap aluminum, nickel, and tin alloys has been included in the secondary copper statistics since 1939, but separate figures showing the recovery from each of these sources are reported in this chapter for the first time.

Recovery of unalloyed copper from scrap continued to decrease, with 114,647 short tons recovered as metal in 1942, compared with 135,869 tons in 1941 and 170,839 tons in 1940. Secondary copper refined at primary plants dropped another 15 percent in 1942 to 85,143 short tons, the smallest production in 10 years, despite Federal

encouragement of copper refining from low-grade brass.

The secondary copper content of brass and bronze reclaimed from purchased scrap rose to 779,062 short tons in 1942, an increase of 36 percent over the 574,267 tons recovered in copper-base alloys during 1941. The secondary copper content of aluminum-base alloy products was more than doubled in 1942, with 13,894 tons of copper reclaimed from scrap in this manner, compared with 5,749 tons in 1941. Unalloyed copper scrap was allocated to both primary and secondary aluminum producers in 1942 in lieu of refined copper for alloying, and the copper contained in aluminum-alloy scrap was also used to advantage in bringing total copper content of aluminum alloy ingots up to specifications.

Almost all of the increase in recovery of secondary copper in 1942 was attributed to new scrap, which rose 60 percent to 500,633 tons of recoverable copper, compared with 313,697 tons of copper in new scrap reprocessed during 1941, whereas recovery of copper from old

scrap gained only 3 percent in 1942.

A total of 220,217 tons of copper was reclaimed from unalloyed copper scrap. Relatively little of this emerged in unalloyed metal products, for clean copper scrap was consumed largely in the production of brass and bronze, chemicals, and aluminum alloys.

Secondary copper recovered in the United States, 1941-42, in short tons

Secondary copper i	ecovered		Recoverable copper content of scrap				
Form of recovery	1941	1942	Kind of scrap processed	1941	1942		
As unalloyed copper: At primary plants At other plants	99, 675 36, 194 135, 869	85, 143 29, 504 114, 647	New scrap: Copper-base Aluminum-base Nickel-base Tin-base	310, 147 2, 805 744	492, 392 7, 389 851		
In brass and bronze In alloy iron and steel	574, 267 (1)	779, 062 1, 164		313, 697	500, 633		
In aluminum alloysIn other alloysIn chemical compounds	5, 749 707 9, 804 590, 527	13, 894 1, 533 17, 455 813, 108	Old scrap: Copper-base Aluminum-base Nickel-base Tin-base	409, 947 2, 201 433 118	424, 441 1, 973 633 75		
	726, 396	927, 755		412, 699	427, 122		
				726, 396	927, 755		

<sup>1</sup> Not available.

Analysis and production of secondary copper and copper-alloy products in the United States, 1941-42

Item produced from scrap		Approximate analysis (percent)						Gross weight pro- duced (short tons)	
nem produced from strap	Cu	Sn	Pb	Zn	Ni	Al	1941	1942	
Refined copper (electrolytic grade)	100						109, 368	102, 975	
Casting copper	99						18, 700	7, 938	
Copper sheet, rod, tubing, etc	99						3, 855	724	
Copper powder	98				4		2, 493	1, 165	
Copper castings	98						1, 453	1,845	
Total unalloyed copper products							135, 869	114, 647	
Brass and bronze ingots:									
Tip pronze	. 88	10		2			26, 343	63, 333	
Leaded-tin bronze	. 88	6	1.5	4.5			29, 404	59, 385	
Leaded red brass	85	5	5	5			91, 389	98, 405	
Leaded semired brass	81	3	7	9			30, 829	19, 323	
High-leaded-tin bronze	. 80	10	10				25,005	26, 032	
Do	. 84	6	8	2			8,658	10, 329	
Do Do	. 75	5	20				5,850	5, 717	
Leaded vellow brass	. 66	1	3	30			21, 518	30, 401	
High-strength vellow brass	. 58			39		1	31, 676	24, 055	
Manganese bronzeAluminum bronze	62		l	27		5	8, 202	44, 572	
Aluminum bronze	89					10	4, 261	10, 038	
Nickel silver	. 58	2	7	18	14		941	533	
Do	65	4	3	5	22		2, 205	579	
Do Gilding metal	. 95			5			5, 231	347	
Low brass	. 80			20			1, 129	1, 310	
Silicon bronze	. 92			4				1,979	
Conductor bronze	94	2	2	2				1, 529	
Hardeners and special alloys	. 81						6, 380	4, 793	
Total copper-alloy ingots							299, 021	402, 660	
Brass and bronze sheet, rod, tubing, etc							1 308, 407	1 531, 159	
Brass and bronze castings							2 152, 637	3 111, 631	
Copper in chemical products (content)	1			1		1	9,804	17, 455	

1 Gross weight of secondary brass and bronze in commercial shapes; included 221,492 tons of copper, 1,200 tons of nickel, 4,166 tons of lead, 236 tons of tin, and 81,313 tons of zine in 1941, and 370,837 tons of copper, 379 tons of nickel, 5,489 tons of lead, 273 tons of tin, 154,107 tons of zine, 72 tons of aluminum, and 2 tons of antimony in 1942.

<sup>2</sup> Gross weight of secondary brass and bronze castings; included 123,955 tons of copper, 1,424 tons of nickel, 9,687 tons of lead, 6,986 tons of tin, and 11,185 tons of zinc in 1941; and 95,224 tons of copper, 602 tons of nickel, 7,235 tons of lead, 5,389 tons of tin, and 3,181 tons of zinc in 1942.

Refined copper of electrolytic grade totaling 102,975 tons was produced from purchased scrap at 12 refineries, of which 10 were primary plants. "Casting copper" for foundry use was produced for sale at only 10 plants in 1942, compared with production at 21 plants in 1941.

Secondary brass and bronze ingot production in 1942 totaled 402,660 short tons, an increase of 35 percent over ingot production in 1941, although the number of producing plants dropped from 78 in 1941 to 73 in 1942. This branch of industry comprised 67 concerns in 1942. Counting secondary smelters of aluminum and lead, as well as copper refiners and brass-ingot makers, 112 smelting plants used copper-base scrap.

The types of brass and bronze casting alloys produced to fill wartime requirements in 1942 showed considerable change from 1941. Production of both lead-free and low-leaded tin bronzes more than doubled, and the manufacture of manganese "bronze" was more than 5 times that of 1941, whereas nickel silver virtually disappeared and high-strength yellow brass dropped off.

Producers' stocks of secondary-brass ingots dropped from 14,071 short tons (revised) on hand December 31, 1941, to 13,838 tons on December 31, 1942, and shipments totaled 402,894 short tons.

Consumption of purchased copper and copper-alloy scrap increased 30 percent to 1,308,782 short tons (gross weight) in 1942, compared with 1,004,170 tons used in 1941. Purchased scrap processed by brass mills increased 74 percent, and the quantity consumed by ingot makers and refirers rose 20 percent, whereas consumption by all other users, including foundries and chemical works, dropped 20 percent in 1942 compared with 1941.

Consumption of purchased copper scrap in the United States in 1942, gross weight, in short tons

			Man				
Scrap item		rs, smelt- refiners	Brass	mills	Founds other m	Total scrap used	
	New scrap	Old scrap	New scrap	Old scrap	New scrap	Old scrap	
No. 1 wire and heavy. No. 2 wire, mixed heavy, and light Composition or red brass	8, 077 2, 253 54, 826	63, 921 87, 777 81, 076 1, 598	5, 860 12, 771	6, 244 1, 648	3, 854 1, 791 18, 677	22, 459 10, 077 27, 819 30, 725	110, 415 116, 317 182, 398 32, 323
Railroad-car boxes Yellow brass Auto radiators (unsweated) Electrotype shells	21, 914	114, 808 34, 563 2, 637	462, 072	12, 354	3, 476	4, 709 423 287	619, 333 34, 986 2, 924
BronzeNickel silver	7, 109 107	5, 343 1, 032	6, 285 1, 978	205	744	1,079 37	20, 765 3, 154
Low brass Aluminum bronze High lead brass	2, 209 2, 459	1, 087 4, 079 464	37, 354	424	356 2, 056 14	4, 753 1, 169 1, 997	46, 183 9, 763 2, 475
Low-grade scrap and residues	87, 133	40, 593			20		127, 746
	186, 087	438, 978	526, 320	20, 875	30, 988	105, 534	1, 308, 782

Many foundries that had formerly used scrap turned to specification ingot because war orders had to meet the rigid standards of the Army and Navy, and many of the alloys required were different from those used in commercial practice. Scrap requirements of the ingot makers differed from those of former years in that leaded brass scrap could not be used in production of many alloys such as manganese bronze and high-tin bronzes, which were so much in demand, and there was not enough low-lead brass scrap to fill all needs. Unusually large quantities of refined tin and zinc were consumed in production of brass and bronze casting alloy ingots during 1942, and refined copper consumed for this purpose totaled 13,421 tons, compared with 8,226 tons in 1941, although the total unalloyed copper scrap consumed by brass ingot makers and refiners in 1942 dropped only 1 percent from the quantity used in 1941. Fired cartridge cases constituted approximately 6 percent of the total yellow-brass scrap used by ingot makers.

Consumers' stocks of purchased copper-base scrap in the United States at end of year, 1941-42, gross weight, in short tons

		On h	On hand—		
	Scrap item	Dec. 31, 1941	Dec. 31, 1942		
Unalloyed copper Copper-base alloy low-grade scrap and residues_		15, 981 57, 220 34, 402	10, 019 87, 280 32, 647		
TO IL Programme and a residence		107, 603	129, 946		

<sup>1</sup> Revised figures.

Consumers' stocks of purchased copper-base scrap rose 21 percent from 107,603 short tons on hand December 31, 1941, to 129,946 tons on hand December 31, 1942. Although stocks rose approximately one-third at both brass mills and smelters, the total copper-base scrap inventory reported by foundries and other manufacturers decreased by one-third.

Maximum prices for brass and bronze alloy ingots were established by written agreement of individual ingot makers with the Government effective February 1, 1942, but official ceiling prices varied in only a few minor details from those previously adhered to on a voluntary basis by ingot producers. Maximum prices were fixed for 85-5-5-5 at 13.50 cents a pound, 88-10-2 at 19.75 cents, and yellow brass at 11.00 cents a pound delivered in carload lots.

On May 18, 1942, the Federated Metals Division of the American Smelting & Refining Co. announced voluntary reductions ranging from one-half to three-quarters cent a pound on many grades of brass ingot, and all other principal manufacturers immediately followed suit.

Formal price ceilings for brass ingots were fixed by Government decree effective August 19, 1942, bringing the average weighted selling

prices approximately 1.20 cents below March 1942 levels.

The maximum selling prices for unalloyed copper scrap in effect since October 1941 were continued for the first 4 months of 1942, with No. 1 copper scrap set at 10.00 cents a pound f. o. b. point of On February 27, 1942, copper alloy scrap was placed shipment. under formal ceilings, with prices regulated according to 24 definite grades. The top price for No. 1 red compostion was set at 9.50 cents a pound, and that for yellow-brass cast scrap was 7.25 cents.

Refining of copper from yellow-brass scrap was encouraged by amendments to the brass-scrap price schedule on April 17, 1942. The maximum prices of refinery brass were fixed at 9.25 cents a pound of copper content for material assaying 60.01 percent or more, and 9.00 cents a pound of copper content for material assaying 50.01 to 60.00 percent copper, and the need for sorting the yellow grades sold as refinery brass was eliminated.

Copper-base scrap prices were again revised downward on May 11, 1942, and a license was required for dealers selling to consumers. On August 17, 1942, maximum prices for 13 classifications of copperalloy scrap were reduced to their proper relationship to the basic 12-

cent price of electrolytic copper.

The August 17 scrap ceilings were unchanged during the remainder of 1942, but on December 31, 1942, price ceilings were removed from copper-base scrap imported for the Metals Reserve Co.

Dealers' monthly average buying prices 4 for No. 1 copper scrap at New York held at 9.37 cents a pound throughout 1942, but prices for No. 1 red composition scrap declined continuously from 9.64 cents in January to 8.12 cents averaged in August and September, then rose to 8.87 cents a pound in November and December.

According to new orders issued December 31, 1941, copper-base scrap could be purchased by consumers only under authority of the War Production Board, and controls were exercised to insure the most efficient use of materials available. Unalloyed copper scrap was allocated to replace refined copper wherever possible, and factory

<sup>•</sup> Quoted from the American Metal Market.

CONTRACTOR OF THE PARTY OF THE

segregation of brass mill scrap was made mandatory so that the scrap could be remelted at brass mills for re-use in wrought products. Nevertheless, a substantial quantity of wrought-brass scrap became mixed or contaminated and was eventually consumed by brass ingot makers for casting brasses. Although the refining of copper from yellow-brass scrap was subsidized to some extent by the Government, beginning in April 1942, total production of secondary refined copper was less than in 1941.

Demand was strong for unalloyed copper scrap and high-tin bronze scrap throughout 1942, but the supply of leaded bronze and most grades of yellow brass exceeded demand until September, when consumption of refinery brass for the recovery of refined copper on Metals Reserve Co. accounts appeared to have caught up with the

rate of supply in all except the very low grade materials.

A monthly canvass of nonferrous-scrap transactions of scrap-metal dealers was conducted by the Bureau of Mines throughout 1942. Approximately 4,500 dealers, exclusive of peddlers and auto wreckers, were engaged in the trade, and 488,436 short tons (gross weight) of copper and copper-alloy scrap were shipped to consumers during the year. Of the 554,283 tons of scrap received by brass mills from outside sources, only 15 percent, or 85,311 tons, was handled by scrap dealers; but 49 percent of the 812,773 tons of copper-base scrap purchased by all other consumers, including refiners, ingot makers, and foundries, was supplied by the scrap-metal dealers.

Stocks of copper-base scrap in dealers' yards fell from 50,492 short tons on January 1, 1942, to 39,499 tons on February 28, then increased steadily for 10 months to 57,587 tons on hand December 31, 1942.

Brass and copper scrap imported into and exported from the United States, 1941-42, in short tons

		1941	1942
Brass scrap imported		 3, 596	6, 669
Scrap copper imported Brass scrap exported Scrap copper exported	 	2, 113 722 3, 259	912 168 2, 233
Surap copper caperious		9,200	

#### SECONDARY NICKEL

Secondary nickel recovered from nonferrous scrap totaled 4,142 short tons valued at \$2,899,400, compared with 5,315 tons valued at \$3,720,500 in 1941. The value in both years was computed at 35.0 cents a pound, the spot-delivery price of electrolytic nickel, including duty.

Production of secondary Monel-metal pig and shot increased from 289 tons in 1941 to 2,564 tons in 1942, but secondary copper-nickel-shot production dropped from 1,873 tons averaging 48 percent nickel

in 1941 to 1,154 tons averaging 40 percent nickel in 1942.

Restrictions on the use of nickel in nonferrous alloys showed their effect in the declines registered in secondary products as well as in decreased consumption of all types of nonferrous nickel-bearing scrap, with the single exception of Monel metal. Total consumption of scrap dropped to 7,908 short tons, of which 60 percent was new scrap and 40 percent was old scrap. Scrap-metal dealers complained

during 1942 that there was little outlet for the nickel-silver scrap they had collected, but dealers' shipments of pure nickel scrap and Monel to consumers totaled 3,297 tons.

Secondary nickel (nonferrous) recovered in the United States, 1941-42, in short tons

Secondary nickel r	ecovered		Recoverable nickel content of scrap			
Form of recovery	1941	1942	Kind of scrap processed	1941	1942	
As metal	248 1, 267 3, 396 (2)	90 2, 230 1, 470 114	New scrap: Nickel-base Copper-base	1, 904 1, 277	1, 698 732	
In chemical compounds	404	238		3, 181	<b>2, 43</b> 0	
	5, 315	4, 142	Old scrap: Nickel-base Copper-base	1,670 464	1, 373 339	
				2, 134	1,712	
	14,554			5, 315	4, 142	

<sup>1</sup> Includes only nonferrous nickel scrap added to cast iron.

Not available.

Consumption of purchased nickel scrap in the United States in 1942, gross weight, in short tons

Scrap item	Remelters, smelters, and refiners		Manufact foun	Total scrap	
. 1801 - 1915 - 1915 - 1915 - 1915 - 1915 - 1915 - 1915 - 1915 - 1915 - 1915 - 1915 - 1915 - 1915 - 1915 - 19 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916 - 1916	New scrap	Old scrap	New scrap	Old scrap	useu
Pure nickel Monel metal Nickel silver Miscellaneous nickel alloys Nickel residues	137 2, 118 107 174	48 1, 243 1, 032 208	64 27 1,978 48 64	83 296 37 49 195	332 3, 684 3, 154 479 259
	2, 536	2, 531	2, 181	660	7,908

Priority control over nickel was tightened on April 1, 1942, by an order prohibiting the use of nickel in many items. In the same month, conservation of nickel in waste materials was attempted by means of regulations that ordered segregation of nickel-bearing scrap, both ferrous and nonferrous, as to grades and degrees of nickel content. On October 3, 1942, the use of nickel was restricted to implements of war except under special authorization.

The Government ceiling prices established in 1941 for nickel scrap continued in force throughout 1942. In April, imported nickelbearing scrap and secondary nickel materials were placed under the maximum selling price regulations, but the Metals Reserve Co. was permitted to purchase manufacturers' unused stocks of metallic nickel without regard to established ceilings. In July, a maximum price of 46 cents a pound for new and 43 cents a pound for partly used nickel anodes was set for Metals Reserve Co. purchases from platers.

Dealers' buying prices for nickel clippings and sheet scrap in New York were quoted at 25 cents a pound until the first week in July, then dropped to 21 cents a pound for the remainder of 1942. Monel clippings were quoted in the New York market at 18 cents for the first 6 months and 16 cents a pound thereafter.

Consumers' stocks of purchased nonferrous nickel scrap<sup>1</sup> in the United States at end of year, 1941-42, gross weight, in short tons

			On hand—		
	Scrap item			Dec. 31, 1941	Dec. 31, 1942
Unalloyed nickel Nonferrous nickel alloys Nickel residues				60 <b>3,</b> 965 485	65 2, 282 500
				4, 510	2, 847

Includes nickel-silver scrap.

No imports of nickel scrap were reported, but exports totaled 4,498 short tons in 1942. Export figures for 1941 were available only for the period July 1 to December 31, and totaled 944 short tons.

#### SECONDARY LEAD

Secondary lead recovered in all forms in 1942 totaled 323,001 short tons valued at \$40,698,126, a drop of 19 percent from recovery in 1941, which totaled 397,416 short tons valued at \$45,305,424. Values were computed at 6.3 cents a pound in 1942 and at 5.7 cents a pound in 1941. Production of soft lead, including refined lead, remelt lead, and lead foil totaled 68,870 short tons in 1942, a decrease of 9 percent from the 75,292 short tons produced in 1941. Secondary antimonial lead production decreased 19 percent to 182,839 tons with a lead content of 170,559 tons.

Secondary lead recovered in the United States, 1941-42, in short tons

Secondary lead recovered			Recoverable lead content of scrap			
Form of recovery	1941	1942	Kind of scrap processed	1941	1942	
As metal: At primary plantsAt other plants	13, 454 61, 810	12, 856 55, 746	New scrap: Lead-base	9, 469 7, 662 5	8, 569 5, 844	
	75, 264	68, 602		17, 136	14, 413	
In antimonial lead <sup>1</sup>	206, 522 88, 200 26, 406 1, 024	170, 559 58, 834 24, 518 488	Old scrap, lead-base: Battery-lead platesAll other lead-base	198, 036 162, 445 19, 769	159, 868 131, 456 16, 900	
	322, 152	254, 399	Tin-base	30	364	
	397, 416	323, 001		380, 280	308, 588	
				397, 416	323, 001	

<sup>&</sup>lt;sup>1</sup> Includes 13,862 tons of lead recovered in antimonial lead from secondary sources at primary plants in 1941 and 11,561 tons in 1942.

Production of secondary lead, tin, and lead- and tin-alloy products in the United States in 1942, gross weight, in short tons

경하고 교육 회사 기계 가는 그 사이트 교관 원	Gross weight of product	Secondary metal content				
		Lead	Tin	Anti- mony	Copper	
Refined pig lead	58, 935 9, 894 41	58, 922 9, 680 41		9		
	68, 870	68, 643		9		
Refined pig tinRemelt tinTin foil	155 386 7		152 379 7			
	548		538			
Lead and tin alloys:  Tinny lead (2 to 10 percent tin) Antimonial lead (to 2 percent antimony) Antimonial lead (2 to 4 percent antimony) Antimonial lead (4 to 8 percent antimony) Antimonial lead (over 8 percent antimony) Common babbitt. Genuine babbitt. Other tin babbitts. Solder (to 15 percent tin) Solder (15 to 30 percent tin) Solder (over 30 percent tin) Linotype metal. Other type metals. Miscellaneous lead-tin alloys	26, 043 27, 001 68, 075 61, 720 15, 445 2, 265 4, 117 13, 188 6, 967 8, 087 20, 191	1, 631 25, 649 26, 122 63, 636 55, 152 11, 695 453 35 9, 549 4, 497 6, 730 17, 011 2, 871	112 21 30 201 85 1, 977 1, 546 51 524 3, 598 2, 457 468 1, 141 2, 082	373 849 4, 238 6, 483 1, 696 197 4 23 39 12 888 2, 031 1, 317	766	
Composition foilTin content of chemical products	261, 208 1, 364 303	228, 600 1, 281	14, 293 79 303	18, 150 4	18	

The decrease in lead and lead alloys recovered from purchased scrap in 1942 resulted not only from a diminished supply of some types of scrap, but also from Government restrictions on civilian consumption that were designed to conserve lead, tin, and antimony for possible war needs.

Orders that enabled the Government to direct the distribution of lead and tin scrap by allocation were issued on January 8, 1942, and as of January 10, 1942, a conservation order prohibited the use of lead in a definite list of civilian manufactures and curtailed the amount to be used in some of the more essential items. Priority control of secondary lead was incorporated in the regulations on May 18, 1942.

Secondary white-metal smelters were quite active during the first 6 months of 1942, apparently in the belief that lead would be used more widely in war production and as a substitute for scarcer metals. Increased consumer demand failed to materialize, with the result that working funds were tied up in large inventories of finished and semi-processed white-metal alloys, and during July and August many of the secondary lead plants were virtually shut down. When it was found that the lead supply was not as critical as had been anticipated, restrictions were relaxed somewhat beginning November 11, 1942, and were further eased on May 26, 1943.

Of the 276 plants engaged in remelting, smelting, and refining scrap lead and lead alloys during 1942, only 251 produced white-metal products, and the other 25 consumed lead and tin scrap in brass and bronze ingot alloys. A total of 361 manufacturers and foundries con-

sumed purchased lead or lead-alloy scrap in their operations but accounted for only a small portion of the secondary metal recovered.

Lead-base scrap consumed in 1942 totaled 396,531 short tons (gross weight), a decrease of 16 percent from the 474,278 short tons processed in 1941.

Consumption of purchased lead scrap in the United States in 1942, gross weight, in short tons

Scrap item	Remelters, smelters, and refiners		Manufacturers and foundries		Total scrap	
	New scrap	Old scrap	New scrap	Old scrap	useu	
Soft lead	80	39, 125 18, 323	219 6	1,087 116	40, 511 18, 445	
Cable leadBattery-lead platesMixed common babbitt		15, 074 221, 573 5, 923		121 9 5, 088	15, 195 221, 582 11, 011	
Solder and tinny lead		7, 313 20, 646	4,026	215 43	11,554 20,689	
Dross	7,479 118	42, 495 1, 064 5, 508	81	799	50, 055 1, 981 5, 508	
	7, 677	377, 044	4, 332	7, 478	396, 531	

Manufacturers and foundries treated 3 percent (11,810 short tons) of the total lead-base scrap, whereas remelters, smelters, and refiners handled 97 percent (384,721 short tons). The decrease in consumption of battery-lead plates and hard-lead scrap accounted for more than two-thirds of the total decline in consumption of all lead-base scrap in 1942.

Stocks of purchased lead and lead-alloy scrap held by remelters, smelters, and refiners increased 31 percent, and inventories of manufacturers and foundries gained 1 percent from the beginning to the end of 1942, bringing the over-all increase in total stocks at all plants to 30 percent, from 41,150 tons to 53,460 tons. A similar picture was noted in stocks of scrap lead and tin held by scrap-metal dealers, which gained 28 percent in 1942.

Consumers' stocks of purchased lead-base scrap in the United States at end of year, 1941-42, gross weight, in short tons

		On h	and—
	Scrap item	Dec. 31, 1941	Dec. 31, 1942
Unalloyed lead		 2, 733 25, 642 12, 775	5, 231 35, 357 12, 872
		41, 150	53, 460

Flow of scrap lead and lead alloys in the scrap metal dealer trade was steady during the first 9 months of 1942 but rose sharply to a peak in October, only to drop back to normal levels in November and December.

On January 15, 1942, price ceilings were imposed on primary lead, secondary lead, and lead-base scrap. Maximum selling prices were set in relation to base prices fixed for each of 146 main shipping points

in 34 States. The base price was that of primary pig lead fixed at 6.50 cents a pound, f. o. b. New York, with the ceiling for heavy lead scrap in New York at 5.95 cents a pound. In general, the ceiling prices for scrap lead closely approximated the market prices prevailing at that time.

Dealers' buying prices for heavy lead scrap in New York averaged 5.51 cents a pound in January but rose to 5.62 cents in February and held this level through June. In July the price dropped to 5.39 cents owing to decline in demand. The price fell again in September to a low of 5.37 cents, which continued for the remainder of 1942.

Dealers' quotations for battery plates rose from 3.20 cents to 3.30 cents during January and held steady until May, when the price declined to 3.25 cents a pound. In July the price dropped to a low of 2.87, which was maintained to the end of the year.

Smelting charges for battery lead plates appeared to be nominal in the first half of 1942 but on July 16 were quoted at \$24 a ton. In August the figure rose to \$25, and this charge was carried through September and October.

Imports of lead scrap totaled 1,305 short tons in 1942, compared with 1,331 short tons in 1941; exports in both years were negligible.

### SECONDARY TIN

Secondary tin recovered from scrap in 1942 totaled 37,918 short tons valued at \$39,434,720, compared with 42,033 short tons valued at \$43,722,726 in 1941. The value was calculated at 52.0 cents a pound in 1942 and at 52.01 cents in 1941.

Tin recovered as unalloyed metal dropped 2 percent, to 5,799 short tons, in 1942, compared with 5,900 tons recovered as metal in 1941; and the secondary-tin content of solder and tin babbitt produced in 1942 was almost halved in comparison with 1941 totals. Secondary tin in chemical compounds produced during 1942 was less than one-third the total reported in 1941, but tin recovered from scrap in lead-base alloy products and in bronze increased 38 and 16 percent, respectively, compared with 1941 figures.

Secondary tin recovered in the United States, 1941-42, in short tons

Secondary tin recovered			Recoverable tin content of scrap			
Form of recovery	1941	1942	Kind of scrap processed	1941	1942	
As metal: At detinning plants At other plants	5, 089 811	5, 261 538	New scrap: Tin plate Tin-base Lead-base	6, 094 3, 277 36	4, 896 2, 980 1, 796	
In solder	5, 900 12, 361	6, 579	Copper-base	3, 020 12, 427	4, 385 14, 057	
In tin babbitt In chemical compounds In lead-base alloys In brass and bronze	3, 145 1, 138 4, 499 14, 990	1, 597 303 6, 196 17, 444 32, 119	Old scrap: Tin cans	121 6, 463 9, 473 13, 549	597 3, 490 7, 871 11, 903	
·	42, 033	37, 918	ooppu buss	29,606	23, 861	
			·	42, 033	37, 918	

Consumption of purchased tin scrap in the United States in 1942, gross weight, in short tons

Scrap item	Remelters, smelters, and refiners		Manufact foun	Total scrap	
- 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 19 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 1925 - 192	New scrap	Old scrap	New scrap	Old scrap	used
Block-tin pipe, scrap, and foil	33 4, 238	929	25 9	103	1, 090 4, 247
Righ-tin babbitt Residues Miscellaneous tin alloys	44 771	318 2,507 23 540		15 161	319 2,566 955 540
	5, 086	4, 317	34	280	9, 717

Supplies of block-tin scrap and high-tin alloy scrap could not keep up with demand in 1942, particularly the need for additional tin in bronze ingots made to Army and Navy specifications. The use of scrap and secondary tin as a substitute for virgin tin was encouraged and was made mandatory in revised Government orders issued January 9, 1943, which stated that no product should be manufactured of pig

tin if secondary tin could be substituted.

Secondary lead-tin and lead-tin-antimony alloys such as type metals and lead-base bearing metals were in poor demand throughout the year owing to restrictions on their use, and stocks of these alloys were built up by both scrap dealers and secondary smelters to such an extent that toward the end of 1942 a program was devised for separation of the tin content as refined tin, with the lead and antimony to be recovered as antimonial lead. Purchases of idle stocks of type metals and bearing metals for recovery of tin began in April 1943, with the National Lead Co. acting as agent for the Metals Reserve Co.

Consumers' stocks of purchased tin-base scrap in the United States at end of year, 1941-42, gross weight, in short tons

Scrap item	On hand—		
Strap item	Dec. 31, 1941 1	Dec. 31, 1942	
Unalloyed tin	77 431	124 604	
Drosses and residues	1, 160	1, 199	
	1,668	1, 927	

<sup>1</sup> Revised figures.

Manufacturers' stocks of jewelers' metal, after having been frozen on February 14, 1942, were collected for the account of Metals Reserve Co. and melted into bar tin and tin alloy for allocation as a substitute for primary pig tin. The metal thus recovered was not included in statistics covering scrap or secondary tin, inasmuch as this procedure represented merely a redistribution of metal already measured as part of the total supply.

Beginning April 7, 1942, consumers were required to turn in a used collapsible tube for each new tube of toilet preparations purchased, and the collections were shipped to the Tin Salvage Institute, Newark, Acting as agent of the Metals Reserve Co., this plant produced its first "tin alloy" pigs in July and by the end of 1942 had reclaimed

324 short tons of secondary pig metals containing 231 short tons of tin. The dealers' buying price for block-tin pipe at New York held steady at 45.50 cents a pound throughout all of 1942, compared with an aver-The ceiling prices of 52.00 cents a pound age of 46.35 cents in 1941. for Grade A pig tin and 51.625 cents for Grade B pig tin that had been fixed in 1941 were continued, and both grades sold at ceiling prices throughout 1942. Although there were no formal maximum prices for tin scrap, selling prices were held in line by virtue of the ceiling on pig tin.

According to orders issued January 8, 1942, the Government was enabled to direct the source, amount, or destination of deliveries of scrap tin and tin-bearing alloys, and scrap dealers' transactions were made dependent on the ratio between scrap shipments and stocks on

the basis of a 60-day turnover.

Detinning plants.—The drop in recovery of tin from new tin-plate clippings at detinning plants in 1942 reflected a 16-percent decrease in the quantity of new clippings available; and although the processing of used tin cans brought the total weight of material treated by detinners almost as high as the 1941 figure, total recovery of tin by detinners dropped 9 percent, from 6,156 short tons in 1941 to 5,492 short tons in 1942.

On October 20, 1942, over 400 municipalities in 15 Northeastern States were ordered to collect prepared cans offered in trash collections. Housewives were urged to wash, cut open, and flatten the cans and to The campaign met keep them in separate containers for collection. with indifferent success in many areas owing to the difficulties of collection, lack of transportation facilities, and careless preparation of some of the cans.

Secondary tin recovered at detinning plants in the United States, 1941-42

]	1941	1942
Scrap treated:		
Clean tin platelong tons_ Old tin- coated containersdo	341, 075 5, 963	287, 660 51, 721
	347, 038	339, 381
Tin recovered as metal:  New tin-plate clippings	5,020 69 1,067	4, 664 597 231
	6, 156	5, 492
Weight of tin compounds produceddoAverage quantity of tin recovered per long ton of clean tin-plate scrap usedpoundsAverage quantity of tin recovered per long ton of old tin-coated containers	1, 927 35. 69	484 34. 0
Average delivered cost of clean tin-plate scrapper long ton	\$18.51 (1)	23. 0 \$18. 9 \$12. 3

<sup>1</sup> Data not available.

In addition to the 7 detinning plants listed in the 1941 edition of this chapter, one other, the Fred L. Hazelquist Manufacturing Co., in Camden, N. J., engaged in detinning activities during the first half of 1942 and recovered tin oxide from old tin cans. Six additional detinning plants, to be located in New York, Buffalo, Birmingham, Chicago, Dallas, and Los Angeles, were planned for Federal construction, but building was halted, after little more than ground-clearing

THE REPORT OF THE PERSON OF TH

operations had taken place, when it was found that collections of old cans in metropolitan areas could scarcely supply existing facilities. One new shredding plant at Carteret, N.J., was built to prepare "green" cans from the New York area for detinning and was not completed until early in 1943, and three others, at Houston, Kansas City, and Dallas, were constructed to shred cans for copper-precipitation plants.

Imports of tin-plate scrap totaled 24,082 long tons, compared with 22,600 long tons in 1941. Exports of tin-plate scrap, circles, wastewaste, and clippings were only 4,639 long tons in 1942; 14,204 long

tons in 1941.

## SECONDARY ANTIMONY

Secondary antimony recovered in 1942 totaled 18,200 short tons valued at \$5,663,840, compared with 21,629 short tons valued at \$6,056,120 in 1941. The value was computed at 15.56 cents a pound, the average selling price for ordinary brands of American-grade antimony in 1942, and at 14.00 cents in 1941.

The 16-percent decline in secondary-antimony recovery in 1942 was attributed to the decreased demand for many of the secondary antimony-bearing alloys usually produced and to reduction in the antimony content of many products (especially battery grids) in

accordance with Government orders.

Of the total secondary antimony recovered in 1942, all but 3 tons was recovered from old scrap. Remelters, smelters, and refiners accounted for 96 percent of the total recovery, and manufacturers and foundries salvaged the other 4 percent.

Secondary antimony recovered in the United States, 1941-42, in short tons

Secondary antimony	recovered		Recoverable antimony content of scrap			
Form of recovery	1941	1942	Kind of scrap processed	1941	1942	
In antimonial lead	15, 409 5, 842 378	11, 943 6, 019 201 37	New scrap: Lead-base Tin-base	5 <u>4</u> 3	(i) 3	
In copper-base anoys	21, 629	18, 200		57	3	
			Old scrap: Lead-base Tin-base	21, 283 289	18, 017 180	
				21, 572	18, 197	
et de la composition br>La composition de la				21, 629	18, 200	

<sup>1</sup> Less than 1 ton.

Production of lead-base and tin-base alloy products containing secondary antimony may be found in a table in the section of this chapter relating to secondary lead. Secondary antimony incorporated in lead and tin products totaled 18,154 tons, of which 66 percent was in antimonial lead.

Battery lead plates, the principal source of secondary antimony, provided 56 percent (10,237 tons) of the antimony reclaimed from scrap in 1942, all of which was apparently recovered in antimonial lead products. Other types of lead-alloy scrap, such as lead babbitts, hard lead, cable lead, type metals, and drosses, supplied 43 percent

(7,780 tons) and tin-base scrap 1 percent (183 tons) of the total

secondary antimony.

Effective January 15, 1942, the maximum price permitted to be charged for the antimony content of antimonial lead was 14.00 cents a pound, but a revision in the price schedule effective April 1 increased the ceiling price to 15.50 cents a pound, and this price remained un-

changed for the remainder of 1942.

Government regulations put antimony under full priority control on May 1, 1942. The order prohibited use of antimony in paints, toys, or ornamental objects and limited the quantity of new antimony in automobile batteries to 7 percent of the total used for batteries in any month, with the balance to be obtained from antimony-bearing scrap or secondary alloys. When the supply of antimony became relatively more plentiful toward the middle of 1942, the regulations were liberalized, on July 11, to permit substitution of antimony for tin in bearing metals and other alloys. Effective August 8, 1942, the maximum antimony content of battery grids was raised from 7.5 to 12 percent by weight if only secondary antimonial lead was used in their production.

SECONDARY ZINC

Secondary zinc recovered from purchased scrap and residues totaled 330,526 short tons with a value of \$57,511,524 calculated at 8.7 cents a pound, the average selling price for the year of all grades of refined zinc. This represents an increase of 16 percent over the 1941 recovery of 283,967 tons, worth \$42,595,050 at an evaluation of 7.5 cents a pound. The figures for recovery include zinc recovered as unalloyed zinc, the zinc content of chemicals, and secondary zinc in aluminum alloys, in brass and bronze, and in zinc-base alloy products.

The over-all gain in secondary zinc was caused by a tremendous expansion in the brass industry, which saw the recovery of zinc in brass from brass scrap rise 61 percent, whereas zinc recovered from zinc-base scrap and residues was 20 percent less in 1942 than in 1941.

Secondary zinc recovered 1 in the United States, 1941-42, in short tons

Secondary zinc rec	overed		Recoverable zinc content of serap					
Form of recovery	1941	1942	Kind of scrap processed	1941	1942			
As metal: By distillation: Slab zine Zinc dust By remelting	59, 306 18, 950 11, 400	52, 712 17, 685 11, 048	New scrap: Zinc-base Copper-base Aluminum-base	122, 577 80, 236	95, 296 162, 242			
Dy temetome	89, 656	81, 445		202, 813	257, 539			
In zinc-base alloys In brass and bronze In aluminum-base alloys	2, 571 143, 220 16	3, 670 212, 038 18	Old scrap: Zine-base Copper-base Aluminum-base	33, 267 47, 877 10	29, 200 43, 787			
In chemical products: Zinc oxide	14, 295	4, 373		81, 154	72, 987			
Zinc sulfateZinc chlorideLithoponeMiscellaneous	2, 840 13, 613 17, 408 348	2, 150 10, 815 15, 750 267		283, 967	330, 526			
	194, 311	249, 081			1			
	283, 967	330, 526						

<sup>&</sup>lt;sup>1</sup> Zinc content.

一一一 一人

Twenty-seven distillers produced 53,195 tons of redistilled slab having an average zinc content of 99.1 percent, a total exceeded only by the 1941 record high of 59,503 tons. The 18,101 tons of zinc dust manufactured from scrap by 10 distillers in 1942 contributed 80 percent of the total zinc-dust production from all sources but represented a decline of 4 percent from the 1941 figure for dust produced from scrap. The drop in production of both redistilled slab and dust was the result of a shortage in raw materials rather than a smaller demand for the products. Two producers of redistilled slab discontinued operations owing to the difficulty of obtaining enough residue for efficient operation.

Production of secondary zinc and zinc-alloy products in the United States, 1941-42, gross weight, in short tons

	Product			1941	1942
Redistilled slab zinc		 	 	59, 503	53, 195
Zinc dust Remelt spelter <sup>1</sup> Remelt die-cast slab			 	18, 950 10, 459 2, 735	18, 101 8, 637 2, 488
Zinc die and die casting alloys Galvanizing stock		 	 	527	1, 403 683
Rolled zinc Zinc powder Zinc in chemical products		 	 	497 78	1, 958 33, 355
Zinc in chemical products		 	 	43, 504	33,

<sup>1</sup> Includes small tonnages of zinc anodes.

Consumption of purchased zinc scrap in the United States in 1942, gross weight, in short tons

Scrap item		s, smelters, efiners	Manufac foun	Total scrap	
	New scrap	Old scrap	New scrap	Old scrap	usca
Clippingssheet and strip	3, 241 293	8, 183 1, 930	2, 398 461	351 80	5, 639 9, 288 2, 010
Skimmings and ashes Dross	43, 353 47, 412		21, 976 11		65, 32 <b>9</b> 47, 423
Die castings.  Flue dust and residues	670 10, 983	14, 203 783	135 10, 364	311 13, 692	15, 319 35, 822
	105, 952	25, 099	35, 345	14, 434	180, 830

The auto-wrecking campaign conducted throughout most of 1942 increased the supply of scrap die castings, and Federal regulations of zinc consumption in the printing trade were responsible for the movement of old engravers' plates. Old zinc scrap composed of die castings, engravers' plates, sheet, strip, and flue dust constituted 22 percent of the total zinc scrap consumed in 1942. Metallic scrap was used in making remelt spelter, zinc alloys, brass, and redistilled zinc.

By the end of 1942, galvanizing activity had decreased to 40 percent of what it had been in the comparable portion of 1941. The net result of this diminished activity was a 20-percent decrease in the supply of galvanizers' skimmings and dross and a lower yield of zinc dust and

redistilled slab in 1942.

Consumers' stocks of purchased zinc-base scrap in the United States at end of year, 1941-42, gross weight, in short tons

	On h	n hand—		
Scrap item	Dec. 31, 1941	Dec. 31, 1942		
Metallic zine scrap. Dross.	1, 378 5, 634	2, 960 4, 232		
Skimmings and residues	32, 433	34, 625		
노릇했다. 본 이 보이 하시다는 아노이 보이 받트	39, 445	41, 817		

The rate of shipment of zinc scrap from nonferrous scrap-metal dealers to consumers increased steadily from the beginning of 1942 until the year's high mark was reached in May, then declined for 4 months before another increase was evident. Zinc scrap handled by dealers consisted for the most part of old metallic scrap, as flue dust and most of the new scrap and residues were shipped directly from

generator to consumer.

Virtually no control was exercised over scrap or remelt zinc during 1942, but early in 1943 a general zinc shortage forced the Government to amend refined-zinc regulations to include remelt zinc in the list of completely allocated materials. At the same time the disposition of all zinc scrap was put under control, and delivery of zinc scrap was not permitted to anyone other than a scrap dealer or a manufacturer for use in the production of redistilled zinc, remelt zinc, brass, zinc dust, zinc oxide, chemicals, or salts unless specific authority to do otherwise was first obtained.

Government control kept prices of zinc scrap in line throughout 1942. Scrap dealers' monthly average buying prices for new zinc clips at New York averaged 6.45 cents a pound during 1942 and ranged from a high of 7.00 cents in March and April to a low average of 5.79 cents in September. Corresponding prices for old zinc scrap in the same market averaged 4.65 cents a pound during 1942, with high and low monthly averages of 5.25 cents in March and April and

3.83 cents in September.

Imports of old zinc scrap totaled 143 short tons, compared with 103 tons in 1941. Imports of residues classed as "zinc dross and skimmings" totaled 353 short tons in 1941 but soared to 3,199 tons in 1942 owing to importation of large quantities of fume from a primary zinc smelter in Canada. Zinc recovered from this fume was not counted as secondary zinc.

# IRON AND STEEL SCRAP 1

By Harold E. Carmony and Herbert L. Cullen

#### SUMMARY OUTLINE

Page   Consumption—Continued.	Page
General summary 543 By type of furnace—Continued.	
Salient statistics Bessemer converters Bessemer converters	556
Prices 545   Electric steel furnaces	556
Legislation 546 Cupola furnaces Air furnaces Air furnaces	558
Stocks 546 Air furnaces Crucible and puddling furnaces	559
Crucible and puddling furnaces	560
Caratiant and an administration of the Diast Inflaces	560
In lerro-andy production	562
Consumption 550 In miscellaneous uses	562
By districts and States 551 Foreign trade	564
By type of furnace 554   World aspects	564
Open-hearth furnaces 554   Review by countries	564

### GENERAL SUMMARY

The continued stimulus of expanding war industries' needs was responsible for a record production of steel ingots in 1942, with consequent greatest demand for iron and steel scrap ever known. The production increased 4 percent over that in 1941. Reflecting this rise, use of purchased ferrous scrap at steel furnaces increased 6 percent over consumption in 1941—the previous record year—although pig-iron production rose 7 percent. During the entire year consumption of scrap remained fairly stable, since steel-ingot production was consistently greater than 95 percent of rated capacity,

the use of scrap reaching a peak in October.

Total consumption of ferrous scrap and pig iron was 3 percent greater than that in 1941. Of the 119,308,034 short tons used, 97,598,709 were charged to steel-making furnaces and 20,443,522 to iron furnaces. In making the average ton of steel in 1942, more pig iron and less scrap were used than in 1941; the relative use of home scrap decreased considerably in 1942 from 1941, but that of purchased scrap increased slightly. The relative decline in the use of home scrap undoubtedly was caused by exportation of large quantities of steel ingots and semifinished steel under lend-lease agreements, which removed potential plant scrap from circulation. In iron furnaces, also, the use of pig iron increased relatively and that of scrap decreased.

During the first 3 months of 1942 stocks of iron and steel scrap declined consistently; however, with the advent of warmer weather the movement of scrap became easier, and there was a gradual uptrend in inventories throughout the remainder of the year. The continued high operating rates in steel production during the year occasioned considerable alarm over the position of domestic stocks of iron and steel scrap. However, the monthly surveys conducted by the

というとは、一般ないというとは、 これのはないというとは、

<sup>&</sup>lt;sup>1</sup> Minerals Yearbook, 1939, p. 513, gives definitions of the various scrap terms used in this report.

Bureau of Mines revealed that available inventories of scrap were rising above the late 1941 lows. The survey of suppliers', producers', and consumers' stocks at the end of 1942 indicated inventories of 7,803,151 short tons, equivalent to 7 weeks' supply at the December rate of consumption. Consumers' stocks of scrap increased from 3,726,030 tons at the beginning of 1942 to 6,316,138 tons at the close. In contrast with the fluctuation in scrap inventories, pig iron stocks were fairly stable.

Prices for scrap remained at the maximums established by the Office of Price Administration early in 1941. According to Iron Age, the quotation for No. 1 Heavy-Melting steel scrap at Pittsburgh was \$20 per gross ton (\$17.86 a short ton) throughout the year, compared

Salient statistics of ferrous scrap and pig iron in the United States, 1941-42

	1941	1942	Change in 1942 (percent)
Stocks, December 31: Ferrous scrap and pig iron at consumers' plants: Home scrap Purchased scrap Pig Iron	Short tons 1, 166, 551 2, 559, 479 1, 585, 199	Short tons 1, 605, 756 4, 710, 382 1, 454, 665	+38 +84 -8
요즘 이번 이번 하는데 모든데 그렇게 되었다.	5, 311, 229	7, 770, 803	-46
Ferrous scrap at suppliers' yards and producers' plants: Prepared scrap Unprepared scrap	675, 952 515, 417	653, 518 833, 495	-3 +62
대통 19. 19. 1일 시민이 되는 모양하는데 다	1, 191, 369	1, 487, 013	+25
Consumption: Ferrous scrap and pig iron charged to— Steel furnaces: 1 Home scrap	26, 433, 206 18, 061, 681 48, 547, 426	26, 731, 787 19, 103, 976 51, 762, 946	+1 +6 +7
Pig iron	93, 042, 313	97, 598, 709	+5
Iron furnaces: <sup>2</sup> Home scrap	7, 471, 474 7, 249, 895 7, 638, 046 22, 359, 415	6, 335, 906 6, 827, 698 7, 279, 918 20, 443, 522	-15 6 5
All furnaces: \$ Home scrap Purchased scrap Pig iron	33, 904, 680 25, 311, 576 56, 185, 472	33, 067, 693 25, 931, 674 59, 042, 864	-2 +2 +5
	115, 401, 728	118, 042, 231	+2
Ferrous scrap (total)	³ 59, 216, 256	³ 58, 999, 367	(4)
Exports:  Iron and steel	888, 340 15, 909	136, 540 5, 196	-85 -67
Scrap: No. 1 Heavy-Melting, Pittsburgh  No. 1 Cast cupola  For export. Pig iron, f. o. b. Valley furnaces:   No. Valley furnaces:  N	\$20. 34 22. 25 18. 74	\$20.00 20.00 23.39	-1 -10 +2
Basic No. 2 Foundry	23. 50 24. 00	23. 50 24. 00	

Includes open-hearth, bessemer, and electric furnaces.
 Includes cupola, air, Brackelsberg, puddling, crucible, and blast furnaces; also direct castings.
 Does not include ferro-alloy and miscellaneous consumption.

Iron Age.

Less than 1 percent decrease.

<sup>&</sup>lt;sup>2</sup> Bureau of Mines Iron and Steel Scrap Monthly Reports: No. 28, Feb. 23, 1943, 5 pp.

with \$20.34 (\$18.16) in 1941. The price of basic pig iron, established at \$23.50 per gross ton (\$20.98 a short ton) at Valley furnaces in

December 1940, prevailed throughout 1942.

• Exports of scrap from the United States in 1942 declined 85 percent from 1941 mainly because exports to countries other than the United Kingdom and the Western Hemisphere were placed under Federal control and because shipping facilities were required for finished war materials.

Figure 1 shows the consumption of purchased scrap and the output of pig iron and steel ingots and castings from 1905 to 1942, inclusive.




FIGURE 1.—Consumption of purchased scrap and output of pig iron and steel in the United States, 1905-42.

Figures on consumption of purchased scrap for 1905-32 are from State of Minnesota vs. Oliver Iron Mining Co. et al., Exhibits, vol. 5, 1935, p. 328; those for 1933-34 are estimates by authors; and those for 1935-42 are based upon Bureau of Mines reports. Figures on output of pig iron and steel are as given by the American Iron and Steel Institute.

## PRICES 3

The ceiling prices for scrap fixed by Price Schedule 4 in 1941 remained effective throughout 1942. Market quotations for both No. 1 Heavy-Melting steel and No. 1 Cast cupola scrap were unchanged

at \$20 per gross ton (\$17.86 per short ton) (Pittsburgh).

There were two minor revisions of the basic price schedule in the early part of 1942. These included adjustments in freight and other transportation charges together with the clarification of open-hearth and electric-furnace grades and unprepared scrap. On February 21, 1942, Price Schedule 4 was revised to incorporate all amendments issued after its promulgation on April 3, 1941, and thereafter was entitled Revised Price Schedule 4. Several minor revisions of Revised Price Schedule 4 that appeared during the year included price adjustments on special grades of scrap, addition of new "remote" scrap areas, modification of shipping-point prices, and definitions of No. 1 Heavy-Melting steel and No. 2 Heavy-Melting steel scrap. Gilding metal-clad steel scrap was exempted from price control effective November 16, 1942, by an amendment to the General Maximum Price Regulation.

Pittsburgh price quotations from Iron Age.

On May 20, 1942, the Office of Price Administration introduced Supplementary Order 5 licensing every dealer selling to a consumer (and in the case of iron and steel scrap, to a consumer or his broker) any waste, scrap, or salvage materials for which maximum prices are established by price schedules.

The price of basic pig iron, established at \$23.50 per gross ton

(\$20.98 per short ton) at Valley furnaces late in December 1940.

remained unchanged throughout 1942.

As the price of scrap exported from the United States was regulated by Revised Price Schedule 4, the price structure remained firm during the entire year. Export-scrap prices in 1942, as indicated by the declared value of iron- and steel-scrap exports, averaged \$23.39 per gross ton (\$20.89 per short ton) for the year, or approximately 25 percent higher than the 1941 average of \$18.74 (\$16.73). 1942 average price was the highest recorded since 1937, when the average was \$18.91 (\$16.88).

#### LEGISLATION

Representative Casey's bill (H. R. 5985, 76th Cong.) to suspend the effectiveness of tariff duties on scrap iron, scrap steel, and non-ferrous-metal scrap was reintroduced without change as H. R. 6531, 77th Congress.<sup>4</sup> It provided for the suspension of tariff duties or import taxes on scrap metal imported for consumption during the period of unlimited national emergency. After debate in both the Senate and the House of Representatives, the bill was approved and became Public, No. 497, 77th Congress, on March 13, 1942. on June 1, 1942, the Division of Industry Operations, War Production Board, acting under an Executive Order, issued an amendment to General Imports Order M-63 to restrict the private importation of scrap metals and to provide for purchase of these materials by Government agencies only.

During the year the Division of Industry Operations issued various amendments to General Preference Order M-24. It was made mandatory to segregate tinned and detinned scrap in certain localities, and the sale or shipment of this type of scrap was prohibited outside the areas of origin, except to a detinning plant or copper-precipitation plant; also, an amendment required the segregation of alloy scrap in the entire country. On May 23, 1942, an amendment was issued that removed the inventory restrictions of Priorities Regulation No. 1 and thereby permitted consumers to increase their inventories of iron and steel scrap without limit. The Division of Industry Operations also issued Limitation Order L-88 on May 18, 1943, restricted the sale as scrap of usable, relaying, and rerolling rails in excess of 10 tons in any calendar month except by permission of the War Production Board.

#### STOCKS

Available stocks of iron and steel scrap and pig iron in the United States at the end of 1942 were determined by the regular annual canvass of consumers of these materials and the monthly canvass of

<sup>&</sup>lt;sup>4</sup> H. R. 6531. A bill to suspend the effectiveness, during the existing national emergency, of tariff duties on scrap iron, scrap steel, and nonferrous metal scrap.

suppliers and producers. The monthly canvass was expanded to include as producers all manufacturers and railroads that produce 50 gross tons of iron or carbon steel scrap, 10 tons of alloy steel scrap, or 1 ton of high-speed steel scrap in a month. The final results of the annual survey indicate that consumers', suppliers', and producers' stocks of iron and steel scrap totaled 7,803,151 short tons on December 31, 1942, which represents a 59-percent increase over the 4,917,399

tons on hand December 31, 1941.

Consumers' stocks.—Consumers' stocks of home and purchased scrap were considerably larger at the end of 1942 than at the beginning. The supply of 1,605,756 short tons of home scrap on hand on December 31 represented a 38-percent increase over the 1,166,551 tons on hand at the beginning of the year, and the supply of 4,710,382 tons of purchased scrap on hand at the end of 1942 was 84 percent more than the 2,559,479 tons on hand December 31, 1941. Thus, consumers' stocks of scrap totaling 6,316,138 tons at the year end were 70 percent larger than the 3,726,030 tons on hand at the beginning of the year.

Consumers' stocks of pig iron totaled only 1,454,665 tons at the end of the year, a decrease of 8 percent from the 1,585,199 tons on

hand at the beginning of the year.

Suppliers' and producers' stocks.—In appraising stocks insofar as suppliers and producers are concerned, it should be noted that the coverage of the canvass is not known precisely. However, the data assembled include virtually complete returns from the larger suppliers and producers, as well as a representative number of returns from others, and the figures shown undoubtedly represent a very substantial part of the total stock of iron and steel scrap in suppliers' and producers' hands.

Stocks held by dealers, automobile wreckers, railroads, and manufacturers increased 25 percent, from 1,191,369 tons on December 31, 1941, to 1,487,013 tons on December 31, 1942. Stocks in the hands of dealers were 37 percent greater at the end of 1942 than at the end of 1941, and manufacturers' inventories gained 20 percent during the

same period.

Consumers' stocks of ferrous scrap and pig iron on hand in the United States on December 31, 1941, and December 31, 1942, by States and districts, in short tons

그러는 그리고 있었다		Decembe	er 31, 1941	1116	December 31, 1942				
State and district		Scrap							
	Home	Pur- chased	Total	Pig iron	Home	Pur- chased	Total	Pig iron	
Connecticut	9, 304	27, 616	36, 920	26, 444	5, 392	34, 199 4, 701	39, 591	14, 534	
Maine Massachusetts Naw Hampshire	14. 988	2, 256 62, 202	2, 337 77, 190	3, 928 77, 773	143 15, 703	84.977	4, 844 100, 680	1, 44 42, 84	
New Hampshire Rhode Island	215	2, 790 7, 706	3,005	1,765	355	2,788	3, 143	64	
Rhode Island	1, 284	7, 706	8,990	12,070 3,722	1,491	9, 556	11,047	5,000	
Vermont	395	4,965			708	9,650	10, 358	1,908	
Total New England	26, 267	107, 535	133, 802	125, 702	23, 792	145, 871	169, 663	66, 38	
Delaware	22, 229	98, 754		44, 536	16, 772	203, 408	220, 180	39, 04	
New York	55, 023	130, 981	186, 004 887, 381	103, 311	44, 596	355, 376	399, 972	90, 44	
Pennsylvania	397, 072	490, 309		334, 786	629, 311		1, 405, 268	392, 81	
Total Middle Atlantic	474, 324	720, 044	1, 194, 368	482, 633	690, 679	1, 334, 741	2, 025, 420	522, 31	
Alabama District of Columbia	33, 479	38, 590	72, 069	40, 111	64, 177	126, 645	190, 822	71, 78	
Kentucky Maryland	31, 477	41, 398	72, 875	29, 377	34, 628	152, 604	187, 232	28, 90	
Florida	833	29, 743	30, 576	5, 508	3, 300	37, 280	40, 580	7, 40	
Miceiceinni	100	275	375	135	26	406	432	9	
North Carolina	159	5, 177	5, 336	1, 212	269	8, 927	9, 196	1, 14	
South Carolina Pennessee	844	2, 143		667	191	8, 161	8, 352	88	
Virginia	15, 422	32, 159		19, 045	6, 642	105, 891	112, 533	12, 31	
West Virginia	6, 176	33, 784	39, 960	26, 250	5, 764	80, 575	86, 339	12, 35	
Total Southeastern	88, 490	183, 269	271, 759	122, 305	114, 997	520, 489	635, 486	134, 88	
Arkansas	} 434	18, 573	19,007	790	787	24, 581	25, 368	40	
Oklahoma Texas	6,806	27, 602	34, 408	1, 385	4, 139	64, 339	68, 478	1,69	
Total Southwestern	7, 240	46, 175	53, 415	2, 175	4, 926	88, 920	93, 846	2,09	
Illinois	111,846	317, 538	429, 384	147, 356	128, 989	522, 538	651, 527	93, 32	
Indiana	103, 529 1, 508	240, 384 30, 765	343, 913 32, 273	99, 170 10, 668	183, 301 3, 534	309, 529 53, 616	492, 830 57, 150	79, 44 10, 34	
Iowa Kansas	1)	1 1 1	100	780	585			92	
Nebraska	863	13, 739	14, 602	780	989	14,054	14, 639	92	
Michigan Wisconsin	89, 521	210, 891	300, 412	237, 570	111, 566	304, 760	416, 326	233, 07	
Minnesota	4,401	51, 767	56, 168	5, 713	10,047	126, 302	136, 349	7, 38	
Missouri	7, 709	69, 168	76, 877	11, 706	3, 378	95, 891	99, 269	8, 75	
North Dakota South Dakota	2,092	274	2, 366	51	2, 038	118	2, 156	4	
Ohio	215, 993	273, 206	489, 199	250, 580	281, 693	634, 767	916, 460	252, 30	
Total North Central	537, 462	1, 207, 732	1, 745, 194	763, 594	725, 131	2, 061, 575	2, 786, 706	685, 60	
Arizona Nevada	2,350	7, 571	9, 921	95	2, 351	16, 600	18, 951	11	
Nevada New Mexico Colorado	] -,000	,,,,,	, ,,,,,,,,		_,				
Colorado Utah	8,093	71, 475	79, 568	9, 130	16, 462	159, 650	176, 112	14, 18	
[daho	130	3, 534	3, 664	52	2	3, 026	3,028	5	
w yoming	5	15, 235	6	2 252	2, 735	1 18, 752	5 21, 487	13	
Montana	1, 279	10, 200	10, 514	202	2, 700	10, 102	21, 401		
Total Rocky Moun- tain	11, 857	97, 816	109, 673	9, 531	21, 554	198, 029	219, 583	14, 49	
Alaska	1		F0.000	0.50		ma 000	00.1==	0.05	
Oregon Washington	5, 573	51,358		2, 740	5, 947	<b>76, 23</b> 0	82, 177	3, 25	
California	15, 338	145, 550	160, 888	76, 519	18, 730	284, 527	303, 257	25, 64	
Total Pacific Coast	20, 911	196, 908	217, 819	79, 259	24, 677	360, 757	385, 434	28, 89	
Total United States	1, 166, 551	2, 559, 479	3, 726, 030	1, 585, 199	1, 605, 756	4, 710, 382	6, 316, 1 <b>3</b> 8	1, 454, 66	
	1.	I	l .	1		l	1	ı	

Suppliers' stocks of iron and steel scrap on hand December 31, 1941, and December 31, 1942, by States and districts, in short tons

	D	ecember 3	1, 1941	December 31, 1942			
State and district	Prepared	Unpre- pared	Total	Prepared	Unpre-	Total •	
Connecticut Maine Massachusetts New Hampshire Rhode Island Vermont	E 004	3, 794 1, 212 17, 959 766 707 1, 793	15, 409 6, 306 31, 899 1, 744 2, 144 4, 258	12, 915 5, 192 18, 449 922 2, 286 3, 031	11, 976 4, 178 27, 962 2, 437 5, 097 2, 620	9, 370 46, 411 3, 359 7, 383	
Total New England		26, 231	61, 760	42, 795	54, 270		
Delaware New Jersey New York Pennsylvania	939 22, 290 54, 783 42, 355	497 16, 416 37, 179 57, 876	1, 436 38, 706 91, 962 100, 231	919 19, 890 47, 453 54, 831	1, 052 19, 660 71, 830 87, 387	1, 971 39, 550	
Total Middle Atlantic	120, 367	111, 968	232, 335	123, 093	179, 929	303, 022	
Alabama District of Columbia Florida Georgia Kentucky Maryland Mississippi North Carolina South Carolina Tennessee Viginia West Virginia	5, 932 482 6, 303 9, 681 8, 533 3, 662 2, 166 7, 108 6, 698 13, 769 15, 970 6, 748	7, 226 1, 392 3, 625 4, 253 6, 255 13, 026 2, 077 2, 727 1, 169 7, 543 8, 505 6, 459	13, 158 1, 874 9, 928 13, 934 14, 788 16, 688 4, 243 9, 835 7, 867 21, 312 24, 475 13, 207	9, 709 826 5, 253 8, 146 10, 443 11, 275 2, 573 10, 942 4, 396 19, 824 10, 918 6, 303	14, 171 1, 440 8, 171 12, 374 11, 336 13, 355 7, 604 7, 822 5, 473 39, 283 13, 236 10, 013	23, 880 2, 266 13, 424 20, 520 21, 779 24, 630 10, 177 18, 764 9, 869 59, 107 24, 154 16, 316	
Total Southeastern	87, 052	64, 257	151, 309	100, 608	144, 278	244, 886	
Arkansas	2, 381 10, 139 5, 376 25, 402	2, 223 7, 954 4, 383 22, 478	4, 604 18, 093 9, 759 47, 880	2, 652 6, 685 9, 390 19, 922	7, 837 12, 086 8, 726 38, 447	10, 489 18, 771 18, 116 58, 369	
Total Southwestern	43, 298	37, 038	80, 336	38, 649	67, 096	105, 745	
Illinois. Indiana Lowa Kansas Michigan Minnesota Missouri Nebraska North Dakota Ohio South Dakota Wisconsin	77, 894 21, 185 8, 644 7, 748 29, 783 67, 650 12, 024 4, 161 784 64, 219 18, 121	48, 768 21, 763 15, 095 7, 699 24, 335 23, 502 17, 720 4, 922 654 47, 804 1, 216 20, 557	126, 662 42, 948 23, 739 15, 447 54, 118 91, 152 29, 744 9, 083 1, 438 112, 023 1, 721 38, 678	42, 373 25, 958 11, 684 7, 951 34, 070 71, 750 10, 764 4, 701 396 47, 496 692 17, 473	52, 624 28, 905 15, 978 13, 141 45, 810 44, 765 16, 494 8, 403 2, 342 57, 890 3, 776 29, 473	94, 997 54, 863 27, 662 21, 092 79, 880 116, 515 27, 258 13, 104 2, 738 105, 386 4, 468 46, 946	
Total North Central	312, 718	234, 035	546, 753	275, 308	319, 601	594, 909	
Arizona Colorado Idaho Montana Nevada New Mexico Utah W yoming	140 5, 872 2, 258 390 334 584 511 5, 443	515 3, 650 644 2, 979 207 17 4, 327 586	655 9, 522 2, 902 3, 369 541 601 4, 838 6, 029	787 5, 969 616 5, 808 29 1, 456 940 1, 328	5, 927 3, 535 985 2, 872 298 1, 789 5, 228 2, 941	6, 714 9, 504 1, 601 8, 680. 327 3, 245 6, 168 4, 269	
Total Rocky Mountain	15, 532	12, 925	28, 457	16, 933	23, 575	40, 508	
California Oregon Washington	43, 130 6, 904 11, 422	19, 602 2, 667 6, 694	62, 732 9, 571 18, 116	37, 768 5, 738 12, 626	32, 427 3, 064 9, 255	70, 195 8, 802 21, 881	
Total Pacific Coast	61, 456	28, 963	90, 419	56, 132	44, 746	100, 878	
Total United States	675, 952	515, 417	1, 191, 369	653, 518	833, 495	1, 487, 013	

#### CONSUMPTION

In the canvass of consumers of ferrous scrap and pig iron in 1942, data were assembled on the scrap used in miscellaneous operations, such as rerolling, reforging, and chemical uses, in addition to that used in remelting processes. To simplify the annual canvass, no details are sought regarding the ordinary trade classifications of scrap consumed, and no attempt is made to obtain data on its value or cost at consumers' plants. Statistics are compiled to show the consumption of scrap and pig iron by districts and States and by types of furnace. To avoid disclosing details concerning individual plants reporting, it is necessary in some instances to combine figures for some States. All such combinations are made with a view to revealing details of consumption by types of furnace rather than by geographic subdivisions.

The importance of scrap in the conservation of resources is illustrated by the relative quantities of scrap and ore used in the domestic iron and steel industry. The total scrap consumed in 1942 was equivalent to 114 percent of the iron content of all domestic and foreign iron and manganiferous ores used in blast furnaces, and purchased scrap alone equaled 51 percent of the iron content of the ores; in 1941

the comparable percentages were 123 and 53.

Scrap constitutes by far the greater part of the ferrous raw materials used in iron and steel plants in the Southwestern, Pacific Coast, and New England districts. These regions, however, used less than 6 percent of the total scrap consumed in 1942. In the New England and Rocky Mountain districts (areas that are small producers of pig iron) and the Southwestern district proportionately more scrap was used in 1942 than in 1941; whereas in the remaining districts (Middle Atlantic, Southeastern, North Central, and Pacific Coast) proportionately less scrap was used.

Open-hearth steel furnaces use by far the largest quantities of ferrous scrap and pig iron. They consumed 66 percent of the total scrap in 1942 (67 percent in 1941), 71 percent of the home scrap (71 percent in 1941), 59 percent of the purchased scrap (63 percent in 1941), and 77

percent of the pig iron (76 percent in 1941).

In cupola furnaces, the second-largest consumers of scrap, the relative consumption of home and purchased scrap was changed considerably. They used 12 percent of the home scrap in 1942 (15 percent in 1941), 19 percent of the purchased scrap (22 percent in 1941), and 8 percent of the pig iron (9 percent in 1941).

Open-hearth and cupola furnaces together consumed 83 percent of the home scrap, 78 percent of the purchased scrap, and 85 percent of

the pig iron in 1942.

Bessemer converters used 10 percent of the pig iron consumed in 1942 but only relatively small quantities of scrap (0.61 percent of the total). Although electric furnaces consumed only 10 percent of the total scrap in 1942, over 98 percent of the total charge to this type of equipment was home and purchased scrap.

Ferrous scrap and pig iron consumed in the United States and percent of total derived from home scrap, purchased scrap, and pig iron, 1941-42, by districts

		1941					1	942		
		Pe	Percent of total used				Percent of total used			
District	Total used (short		Scrap		Pig	Total used (short		Scrap		<b>.</b>
	tons)	Home	Pur- chased	Total	iron	tons)	Home	Pur- chased	Total	Pig iron
New England Middle Atlantic. Southeastern Southwestern North Central Rocky Mountain Pacific Coast	1, 532, 883 40, 056, 774 14, 286, 365 295, 465 55, 915, 636 1, 512, 974 1, 801, 631	31. 9 28. 6 26. 3 25. 1 30. 8 27. 9 25. 4	37.0 19.5 19.8 73.0 22.1 29.5 62.8	68. 9 48. 1 46. 1 98. 1 52. 9 57. 4 88. 2	31. 1 51. 9 53. 9 1. 9 47. 1 42. 6 11. 8	1, 602, 721 42, 029, 787 15, 006, 739 461, 624 56, 464, 226 1, 637, 012 2, 105, 925	30. 9 26. 6 24. 4 22. 0 29. 7 26. 7 21. 1	38. 4 20. 1 19. 9 76. 4 22. 7 32. 6 66. 0	69. 3 46. 7 44. 3 98. 4 52. 4 59. 3 87. 1	30. 7 53. 3 55. 7 1. 6 47. 6 40. 7 12. 9
	115, 401, 728	29. 4	21.9	51. 3	48.7	119, 308, 034	27.8	22.7	50. 5	49. 5

Proportion of home and purchased scrap and pig iron used in furnace charges in the United States, 1941–42, in percent

		19	41						
Type of furnace		Scrap			Scrap				
	Home	Pur- chased	Total	Pig iron	Home	Pur- chased	Total	Pig iron	
Open-hearth Bessemer Electric Cupola Air 1	29. 1 5. 0 49. 6 31. 4 47. 8	19.3 1.2 48.7 34.8 19.1	48.4 6.2 98.3 66.2	51. 6 93. 8 1. 7 33. 8	27. 6 4. 0 50. 5 29. 0	18. 9 1. 7 48. 0 37. 8	46. 5 5. 7 98. 5 66. 8	53. 5 94. 3 1. 5 33. 2	
Crucible Puddling Blast	53.3 5.6 54.7	41.0 27.8 45.3	66.9 94.3 33.4 100.0	33. 1 5. 7 66. 6	48. 8 73. 1 4. 7 53. 3	18. 5 20. 7 30. 3 46. 7	67. 3 93. 8 35. 0 100. 0	32. 7 6. 2 65. 0	

<sup>&</sup>lt;sup>1</sup> Includes data for 3 Brackelsberg furnaces.

#### CONSUMPTION BY DISTRICTS AND STATES

All 48 States, the District of Columbia, and Alaska contain plants consuming ferrous scrap and pig iron. The greatest consumption, however, is concentrated in the steel-making centers of the North Central, Middle Atlantic, and Southeastern States. These areas include the 8 largest consuming States, which used 82 percent of the total scrap, 91 percent of the pig iron, and 86 percent of the total scrap and pig iron charged into furnaces in 1942; the comparable percentages in 1941 were 83, 92, and 87, respectively. These States (the relative position of which varied slightly from 1941) and the percentage of the total ferrous scrap and pig iron each consumed in 1942 were as follows: Pennsylvania 28, Ohio 20, Indiana 11, Illinois 9, New York 5, Alabama 5, Michigan 4, and Maryland 4.

The second table following shows total consumption of ferrous scrap and pig iron by districts and percentage change in use of home scrap, purchased scrap, total scrap, and pig iron, 1938 to 1942.

Consumption of ferrous scrap and pig iron in the United States, 1941-42, by type of furnace, in short tons

됐는데 아이를 나는 다 하는데?	Active				
Type of furnace or equipment	plants re- porting	Home	Purchased	Total	Pig iron
1941				1.00	
Open-hearth	139	24,002,629	15, 920, 857	39, 923, 486	42, 481, 404
Bessemer	_ 33	320, 738	72, 506	393, 244	5, 993, 264
Electric	306	2, 109, 839	2,068,318	4, 178, 157	72, 758
Cupola	2,798	5,004,864	5, 559, 273	10, 564, 137	1 5, 388, 747
Oupola Air Brackelsberg	128	872, 227	349, 425	1, 221, 652	604, 835
Crucible		1.949	1,499	3, 448	207
Puddling		4, 568	22, 626	27, 194	54, 183
Blast		1, 587, 866	1, 317, 072	2, 904, 938	02,200
Direct castings					1, 590, 074
44.14.14.14 <u>.1.</u> 16.4.14.19.1	2 3, 531	33, 904, 680	25, 311, 576	59, 216, 256	56, 185, 472
• 1942 Open-hearth	145	23, 445, 884	16, 114, 069	39, 559, 953	45, 538, 846
Bessemer	33	260, 025	109, 887	369, 912	6, 131, 222
		3, 025, 878	2,880,020	5, 905, 898	92, 878
Electric Cupola Cupola	2,763	3, 936, 603	5, 117, 918	9,054,521	1 4, 490, 513
Air	129	1	212 066	1, 141, 444	555, 436
Brackelsberg	. 3	828, 178	313, 266		
Crucible	13	2,610	741	3, 351	221
Puddling	- 8	3,603	23, 174	26, 777	49, 835
Blast	_ 73	1, 564, 912	1, 372, 599	2, 937, 511	
Direct castings	_ 30				2, 183, 913
Ferro-alloy 3	_ 21	10,853	307, 316	318, 169	19
Miscellaneous 3	_ 137	50, 826	896, 789	947, 615	
	2 3, 701	33, 129, 372	27, 135, 779	60, 265, 151	59, 042, 883

## Consumption of ferrous scrap and pig iron in the United States, 1938-42, by districts

				Ser	ар			Diasi	
		Hon	ne Purchased Total		al	Pig iron			
District and year	Active plants report- ing	Short tons	Change from pre- vious year (per- cent)	Short tons	Change from pre- vious year (per- cent)	Short tons	Change from pre- vious year (per- cent)	Short tons	Change from pre- vious year (per- cent)
New England: 1938	257 263 270 267 271	140, 344 240, 931 283, 607 489, 163 494, 569	+71.7 +17.7 +72.5	385, 805 413, 993 566, 952	+53.8 +7.3 +36.9	626, 736 697, 600 1, 056, 115	+60. 2 +11. 3 +51. 4	239, 753 301, 997 476, 768	-45.6 +64.4 +26.0 +57.9 +3.2
Middle Atlantic: 1938 1939 1940 1941 1942	817 835 831 859 914	5, 840, 586	+50.4 +40.4 +39.9	4, 660, 910 5, 607, 105 7, 796, 243	+57. 0 +20. 3 +39. 0	6, 850, 580 10, 501, 496 13, 804, 979 19, 268, 970 19, 637, 783	+53.3 +31.5 +39.6	6, 617, 829 12, 250, 912 17, 400, 042 20, 787, 804 22, 392, 004	+85.1 +42.0 +19.5
Southeastern: 1938	445 470 473 490 525	2, 593, 437 3, 137, 588 3, 761, 458	+46.9 +21.0 +19.9	2, 019, 620 2, 485, 652 2, 825, 903	+44.9 +23.1 +13.7	4, 613, 057 5, 623, 240 6, 587, 361	+46.0 +21.9 +17.1	5, 853, 055 6, 905, 435 7, 699, 004	+52.9 +18.0 +11.5
Southwestern: 1938	131 132 139	39, 865 39, 674 74, 059	+1.2 5 +86.7	125, 968 135, 909 215, 699	+14.1 +7.9 +58.7	165, 833 175, 583 289, 758	+10.7 +5.9 +65.0	4, 575 4, 434 5, 707	-3.1 +28.7

Includes some pig iron used in making direct castings.
 Where 2 or more separate departments, such as blast-furnace, open-hearth, foundry, etc., are situated at the same place and are operated by 1 establishment, each appears as 1 plant in the total.
 Comparable data not obtained for 1941.

Consumption of ferrous scrap and pig iron in the United States, 1938-42, by districts—Continued

				Scr	ар			Pig i	ron
		Ног	ne	Purch	ased	Tot	al		
District and year	Active plants reporting	Short tons	Change from pre- vious year (per- cent)	Short tons	Change from pre- vious year (per- cent)	Short tons	Change from pre- vious year (per- cent)	Short tons	Change from pre- vious year (per- cent)
North Central: 1938	1, 374 1, 377 1, 424	224, 007	+58.8 +23.5 +34.6 -2.5 -54.3 +119.7	8, 468, 527 9, 622, 839 12, 329, 204 12, 814, 917 161, 999 280, 988	+47.0 +13.6 +28.1 +3.9 -49.2 +73.5	504, 995	+53.3 +19.1 +31.8 +.2 -51.3 +91.3	412, 564	+65.0 +28.5 +26.0 +1.9
1941 1942 Pacific Coast: 1938	75 87 234	421, 191 436, 470 223, 317	+61. 5 +3. 6 -20. 6	446, 745 533, 604 582, 092	+30.9 +19.4 -23.5	867, 936 970, 074 805, 409	+44.2 +11.8 -22.7	645, 038 666, 938 104, 598	+40.8 $+3.4$ $-41.2$
1939 1940 1941 1942	252 258 277 285	326, 872 458, 643	+2.9 +40.3	875, 181 1, 130, 830	+14.7 $+29.2$	1, 202, 053 1, 589, 473	$+11.2 \\ +32.2$	189, 440 212, 158	
United States: 1938 1939 1940 1941 1942	1 3, 393 1 3, 407 1 3, 531	12, 679, 902 19, 621, 896 25, 047, 723 33, 904, 680 33, 129, 372	+54. 7 +27. 7 +35. 4	11, 226, 424 16, 704, 640 19, 481, 948 25, 311, 576 27, 135, 779	+48.8 +16.6 +29.9	23, 906, 326 36, 326, 536 44, 529, 671 59, 216, 256 60, 265, 151	+52.0 +22.6 +33.0	20, 724, 871 35, 232, 699 46, 185, 828 56, 185, 472 59, 042, 883	-45.7 +70.0 +31.1 +21.7 +5.1

 $<sup>^{\</sup>rm 1}$  Where 2 or more separate departments, such as blast-furance, open-hearth, foundry, etc., are situated at the same place and are operated by 1 establishment, each appears as 1 plant in the total.

Consumption of ferrous scrap and pig iron in the United States in 1942, by States and districts

				Scra	p				
	Ac- tive plants	Hom	e	Purcha	sed	Tota	1	Pig iro	n
State and district	re- port- ing	Short tons	Percent of total	Short tons	Per- cent of total	Short tons	Percent of total	Short tons	Per- cent of total
Connecticut Maine Massachusetts New Hampshire Rhode Island Vermont	72 22 127 21 14 15	10, 907 246, 322 5, 727 50, 465	(1) (1) . 2	8, 557	(1) 1.2 .1 .2	19, 464 569, 925 23, 735 101, 559	(1) 1.0 (1) .2	8, 763 244, 993 20, 523 58, 116	(1) (1) (1)
Total New England	271	494, 569	1.5	616, 166	2.3	1, 110, 735	1.9	491, 986	.8
Delaware New Jersey New York Pennsylvania	11 117 248 538	1, 643, 531	5.0	1, 435, 330	5.3		5.1	,	5.1
Total Middle Atlantic	914	11, 190, 820	33.8	8, 446, 963	31.1	19, 637, 783	32.6	22, 392, 004	37.9
Alabama District of Columbia Kentucky Maryland	103 4 28	n i		i		1 ' '	l		1

See footnote at end of table.

556250-43---36

Consumption of ferrous scrap and pig iron in the United States in 1942, by States and districts—Continued

				Scrap	) 			Pig ir	0m
Globa and district	Ac- tive plants	Hom	е	Purcha	sed	Tota	1	rigin	on
State and district	re- port- ing	Short tons	Percent of total	Short tons	Percent of total	Short tons	Percent of total	Short tons	Per- cent of tota
Florida	22 63		0. 2	140, 562	0.5	199, 295	0.3	81, 229	0.
Georgia Mississippi North Carolina South Carolina	12 59 20	678 19, 734 4, 353	(1) .1	1, 867 27, 273 12, 872	(1) .1 .1	2, 545 47, 007 17, 225	(1) (1)	615 16, 076 4, 532	(1) (1) (1)
Pennessee Virginia West Virginia	73 67 37	} 196, 187 380, 539	. 6 1. 1	358, 112 569, 612	1.3 2.1	554, 299 950, 151	. 9 1. 6	165, 331	2.
Total Southeastern	526	3, 669, 073	11. 1	2, 981, 358	11.0	6, 650, 431	11.0	8, 356, 308	14.
Arkansas Louisiana Okiahoma	14 26 72	27, 924	.1	98, 079	. 4	126, 003	.2	3, 053	(1)
Texas	26	73, 759	. 2	254, 381	. 9		. 6		(1)
Total Southwestern	138	101, 683	-3	352, 460	1.3	454, 143			(1)
Illinois Indiana Iowa Kansas	264 165 69 38	113, 355	9.4 11.7 .3	2, 198, 196 235, 803	8.7 8.1 .9	349, 158	9.0 10.1 .6	6, 963, 040 64, 012	9 11
Nebraska Michigan	17	29, 204	. 1 6. 6	75, 131 1, 822, 251	. 3 6. 7		. 2 6. 6		(1)
Wisconsin Minnesota Missouri	82 78	216, 532 227, 074	.7 .7	379, 773 727, 075	1. 4 2. 7	596, 305	1.0 1.6	308, 937	
North Dakota South Dakota Ohio	3 399	1, 103 7, 027, 005	(1) 21. 2	687 5, 001, 404	(1) 18. 4	1, 790 12, 028, 409	(1) 20.0	76 11, 958, 323	(1) 20
Total North Central	1, 480	16, 793, 338	50.7	12, 814, 917	47. 2	29, 608, 255	49.1	26, 855, 971	45
Arizona Nevada New Mexico	9 4 4		.1	56, 022	. 2	73, 996	.1	36	(1)
Colorado Utah Idaho	33 19 6	J 400,010	1.2	444, 469 7, 830	1.7	849, 485 8, 925	1. 4	666, 254 112	(1) (1)
Wyoming Montana	1 11	12, 383	(1)	25, 282	(1) . 1	37, 665	(1)	535	(i)
Total Rocky Mountain	87	436, 470	1.3	533, 604	2.0	970, 074	1.6	666, 938	
Maska	1 43 71	76, 544	. 2		1.2		.6		(1)
California  Total Pacific Coast	285	366, 875 443, 419	1.1	1, 075, 774	3. 9 5. 1	1, 442, 649	3.0	255, 017 272, 195	
Total United States:	-			27, 135, 779		60, 265, 151		59, 042, 883	100
1942 1941	2 3,531	33, 904, 680	100.0	25, 311, 576		59, 216, 256		56, 185, 472	100

#### CONSUMPTION BY TYPE OF FURNACE

Open-hearth furnaces.—Ferrous scrap and pig iron consumed in open hearths in 1942 totaled 85,098,799 tons—a 3-percent increase over 1941. Of the 1942 total, home scrap constituted 27 percent, purchased scrap 19 percent, and pig iron 54 percent. The use of home scrap decreased 2 percent, with the use of purchased scrap and pig iron increasing 1 and 7 percent, respectively.

Less than 0.05 percent.
 Where 2 or more separate departments, such as blast-furnace, open-hearth, foundry, etc., are situated at the same place and are operated by 1 establishment, each appears as 1 plant in the total.

Charges to open-hearth furnaces in 1942 consisted of 46 percent total scrap and 54 percent pig iron, compared with percentages of 48 and 52, respectively, in 1941. Of the total scrap consumed in open hearths in 1942, 41 percent was purchased scrap, compared with 40 percent in 1941 and 41 percent in 1940. Higher proportions of scrap are used in areas remote from pig-iron-producing centers, but the practice of using scrap exclusively is relatively rare. In 1942 only 3 plants out of a total of 145 operated on a 100-percent scrap basis; they consumed only 541,762 tons, less than 1 percent of the total consumption of raw materials in open hearths.

Pennsylvania, the leading steel-producing State, outranked all others in 1942 in the consumption of ferrous scrap and pig iron in

open hearths, followed by Ohio, Indiana, and Illinois.

Consumption of ferrous scrap and pig iron in open-hearth furnaces in the United States in 1942, by districts and States, in short tons

	Active		Scrap		Dia isan
District and State	plants reporting	Home	Purchased	Total	Pig iron
New England:					
Connecticut Massachusetts Rhode Island	2	113,600	264, 374	377, 974	154, 343
Total: 1942	4 4	113, 600 134, 958	264, 374 228, 518	377, 974 363, 476	154, 343 148, 899
Middle Atlantic: Delaware New Jersey New York Pennsylvania.	3 8	1, 420, 892 7, 160, 202	997, 469 4, 495, 210	2, 418, 361 11, 655, 412	2, 849, 286 14, 788, 260
Total: 1942	64 61	8, 581, 094 9, 056, 244	5, 492, 679 5, 369, 913	14, 073, 773 14, 426, 157	17, 637, 546 16, 631, 043
Southeastern and Southwestern: Alabama Georgia Tennessee Oklahoma Texas District of Columbia Kentucky Maryland	1 1 1 1 1 2	943, 265	551, 063 1, 304, 706	1, 494, 328 3, 066, 149	2, 624, 876 3, 980, 770
West Virginia Total: 1942 1941	14 12	2, 704, 708 2, 686, 917	1, 855, 769 1, 834, 492	4, 560, 477 4, 521, 409	6, 605, 646 5, 787, 602
North Central: Illinois Indiana Michigan Iowa Missouri Minnesota Wisconsin Ohio	8 4 1 3 1	2, 122, 889 3, 479, 930 782, 693 } 149, 658 } 182, 984 4, 780, 436	1, 366, 008 1, 809, 941 562, 207 496, 243 243, 376 2, 959, 336	3, 488, 897 5, 289, 871 1, 344, 900 645, 901 426, 360 7, 739, 772	3, 732, 154 6, 406, 822 1, 365, 749 21, 468 285, 129 8, 513, 188
Total: 19421941	56 55	11, 498, 590 11, 567, 667	7, 437, 111 7, 456, 887	18, 935, 701 19, 024, 554	20, 324, 510 19, 196, 973
Rocky Mountain and Pacific Coast: Colorado California Washington	1 5 1	<b>547, 892</b>	1,064,136	1, 612, 028	816, 801
Total: 1942 1941	7 7	547, 892 556, 843	1, 064, 136 1, 031, 047	1, 612, 028 1, 587, 890	816, 801 716, 887
Total United States: 19421941	145 139	23, 445, 884 24, 002, 629	16, 114, 069 15, 920, 857	39, 559, 953 39, 923, 486	45, 538, 846 42, 481, 404

Bessemer converters.—The consumption of ferrous scrap and pig iron in bessemer converters in 1942 totaled 6,501,134 tons—a 2-percent increase over 1941. The proportion of scrap consumed in converter practice is low (amounting to only 5.7 percent in 1942), and the major portion was home scrap. Almost all of the small tonnage of purchased scrap consumed in converters was used in small steel-foundry plants.

Pennsylvania was the principal consumer of scrap in bessemer converters in 1942.

Consumption of ferrous scrap and pig iron in bessemer converters in the United States in 1942, by districts and States, in short tons

District and State	Active		Scrap			
District and State	plants re- porting	Home	Purchased	Total	Pig iron	
New England and Middle Atlantic: Connecticut. Delaware Massachusetts. Pennsylvania	1	4, 128 98, 118	3, 769 55, 924	7, 897 154, 042	2, 511 2, 314, 482	
Total: 1942	13 13	102, 246 107, 508	59, 693 52, 257	161, 939 159, 765	2, 316, 993 2, 201, 311	
Southeastern and Southwestern: Alabama. Maryland West Virginia. Louisiana. Texas	1 1 1 1 1	32, 015	17, 362	49, 377	514, 930	
Total: 1942	5 5	32, 015 63, 088	17, 362 5, 090	49, 377 68, 178	514, 930 488, 351	
North Central and Pacific Coast; Illinois Indiana Iowa Michigan	1	9, 295	15, 517 12, <b>43</b> 7	24, 812 23, 951	586, 453 319, 654	
Minnesota Missouri Washington Ohio	1 1 1	5, 837 99, 118	4, 878	10, 715 99, 118	3, 446 2, 389, 746	
Total: 1942	15 15	125, 764 150, 142	32, 832 15, 159	158, 596 165, 301	3, 299, 299 3, 303, 602	
Total United States: 19421941	33 33	260, 025 320, 738	109, 887 72, 506	369, 912 393, 244	6, 131, 222 5, 993, 264	

Electric steel furnaces.—Ferrous scrap and pig iron consumed in electric furnaces totaled 5,998,776 tons—a 41-percent increase over 1941. Pig iron constituted less than 2 percent of the total ferrous raw materials used in electric furnaces. Of the 346 active plants reporting, 104 operated exclusively on scrap and consumed 942,678 tons—about 16 percent of the total scrap and pig iron used.

Ohio led all States in 1942 in the consumption of scrap in electric furnaces, followed by Pennsylvania, Illinois, Michigan, and California.

Consumption of ferrous scrap and pig iron in electric steel furnaces in the United States in 1942, by districts and States, in short tons

District and Glada	Active			Pig iron	
District and State	plants reporting	Home	Purchased	Total	rig iron
New_England:					
ConnecticutNew Hampshire	6	11, 980	12,800	24, 780	76
Rhode Island	i i	1,551	1, 594	3, 145	7
Vermont	_ 1	l)			
Massachusetts	- 11	35, 911	15, 386	51, 297	1, 28
Total: 1942	20 15	49, 442 30, 946	29, 780 21, 505	79, 222 52, 451	2, 12 1, 63
Aiddle Atlantic:	=====				
Delaware	- 2	86, 574	77, 693	164, 267	2,34
New Jersey New York	20	124, 298 672, 426	131, 741 629, 976	256, 039 1, 302, 402	4, 49
Pennsylvania	_ 60	672, 426	629, 976	1, 302, 402	13, 56
Total: 1942	91	883, 298	839, 410	1, 722, 708	20, 40
1941	84	585, 822	839, 410 674, 863	1, 722, 708 1, 260, 685	22, 72
outheastern: District of Columbia	1				
Kentucky	_ 2	33, 883	63, 105	96, 988	- 48
Maryland	-  4	00,000	00, 100	00,000	
West Virginia	- 1 5	K			
Florida	1 1	17,958	41,065	59, 023	143
Georgia Tennessee	- 3 4	{			
Virginia.	3	23, 995	42, 441	66, 436	1, 15
Total: 1942	- 24 17	75, 836 53, 207	146, 611 122, 688	222, 447 175, 895	1,77 87
outhwestern:					
Arkansas	_ 1	1			•
OklahomaLouisiana	1 4	34,550	47, 456	82,006	65
Texas	8	J			
Total: 1942	- 14 13	34, 550 25, 167	47, 456 35, 625	82, 006 60, 792	65 56
North Central:	25	001 610	310, 385	601, 997	22,05
Illinois Indiana	13	291, 612 41, 703	34, 283	75, 986	79
Iowa	_ 5	1			
Kansas	1 1	18, 625	25, 544	44, 169	14
Nebraska Michigan	31	305, 434	230, 646	536, 080	18, 14
Minnesota	. 4	6, 782	12, 148	18, 930	50
Missouri Ohio	- 10 36	1 074 413	777 699	1 852 112	1, 56 14, 51
Wisconsin	14	6, 782 15, 574 1, 074, 413 101, 719	12, 148 18, 554 777, 699 135, 168	18, 930 34, 128 1, 852, 112 236, 887	8, 43
Total: 1942	140 126	1, 855, 862 1, 339, 762	1, 544, 427 1, 064, 756	3, 400, 289 2, 404, 518	66, 15 45, 93
1941	120	1, 555, 702	1,001,700	2, 101, 010	
Rocky Mountain: Arizona	_ 2	h			
Colorado	_ 2	11, 291	18, 113	29, 404	31
Nevada	1 1	,	-3,	21, 211	
Utah	1	ļ			
Total: 19421941	- 6 - 6	11, 291 10, 337	18, 113 15, 150	29, 404 25, 487	31 11
Pacific Coast:					
Alaska	_ 1	7.27	15, 120	22, 499	1
Oregon	. 6	7,379	1 .		1.36
California Washington	_ 29 _ 15	90, 811 17, 409	185, 177 53, 926	275, 988 71, 335	1,30
Total: 1942	51 45	115, 599 64, 598	254, 223 133, 731	369, 822 198, 329	1, 44 91
Cotal United States: 1942	346	3, 025, 878	2, 880, 020	5, 905, 898	92, 87 72, 75
1941	306	2, 109, 839	2, 068, 318	4, 178, 157	72 75

Cupola furnaces.—Consumption of ferrous scrap and pig iron in cupola furnaces totaled 13,545,034 tons—a 15-percent decrease from 1941. Use of home scrap declined 21 percent, purchased scrap 8 percent, total scrap 14 percent, and pig iron 17 percent. Thus, the proportionate decrease in the use of purchased scrap was less than that of pig iron, undoubtedly owing to the establishment of scrap price lower than the price of pig iron.

Charges to cupola furnaces consisted of 29 percent home scrap, 38 percent purchased scrap, and 33 percent pig iron; in 1941 the percentages were 31, 35, and 34, respectively. Many cupola plants operate on a 100-percent scrap charge; 509 plants reported the use of 699,690 tons of ferrous scrap without pig iron in 1942, compared with 511

plants that reported the use of 922,685 tons in 1941.

The relative position of States that are large consumers of scrap in cupola furnaces was altered in 1942 as compared with 1941. Ohio was the principal consumer, followed in order by Michigan, Pennsylvania, Illinois, Alabama, and New York.

Consumption of ferrous scrap and pig iron in cupola furnaces in the United States in 1942, by districts and States, in short tons

District and State	Active plants re-		Scrap		Pig iron <sup>1</sup>
District and District	porting	Home	Purchased	Total	righton.
New England:					
Connecticut	56	91, 399	62, 066	153, 465	93, 152
Maine Massachusetts	22	10, 907	8, 557	19, 464	8, 763
Massachusetts	104	113, 228	145, 048	258, 276	132, 452
New Hampshire Rhode Island	17	3, 250	16,049	19, 299	18, 623
Vermont	11	30, 402	25, 952	56, 354	30, 341
vermont		19, 494	22, 238	41, 732	20, 653
Total: 1942	224	268, 680	279, 910	548, 590	303, 984
1941	229	266, 473	282, 850	549, 323	294, 792
Middle Atlantic:	<del></del>				
Delaware	5	4,671	6, 684	11, 355	4, 216
New Jersey	82	160, 446	286, 251	446, 697	247, 819
New York	185	238, 659	301, 292	539, 951	277, 079
Pennsylvania	327	395, 377	492, 614	887, 991	607, 456
Total: 1942	599	799, 153	1, 086, 841	1, 885, 994	1, 136, 570
1941		918, 860	1, 187, 215	2, 106, 075	1, 181, 810
Southeastern:					
Alehama	78	318, 762	279, 237	597, 999	795, 096
District of Columbia	2	h '			
Maryland	29	49, 489	64,678	114, 167	57, 609
Florida	21	1,786	5, 135	6,921	1, 419
Georgia	57	26, 538	38, 038	64, 576	28, 893
Kentucky	22	26, 904	26, 097	53, 001	67. 343
Mississippi	12	678	1, 867	2, 545	615
North Carolina	59	19, 734	27, 273	47, 007	16,076
South Carolina	19	4, 353	4, 501	8, 854	4, 532
Tennessee	63	111, 287	119, 208	230, 495	111, 278
Virginia	62	57, 816	162, 117	219, 933	52, 186
West Virginia	24	10, 888	27,879	38, 767	13, 724
Total: 1942	448	628, 235	756, 030	1, 384, 265	1, 148, 771
1941	441	709, 765	693, 029	1, 402, 794	1, 337, 657

See footnote at end of table.

Consumption of ferrous scrap and pig iron in cupola furnaces in the United States in 1942, by districts and States, in short tons—Continued

District and State	Active plants re-		Scrap		Pig iron¹
District and State	porting	Home	Purchased	Total	I ig ii on
Southwestern:					
Southwestern: Arkansas	13	419	1,857	2, 276	78
Louisiana	21	2, 794	6, 311	9, 105	1. 07
Oklahoma	22	5,041	12, 301	17, 342	1, 55
Texas	59	29,694	99, 687	129, 381	1,86
Total: 1942	115	37, 948	120, 156	158, 104	4, 56
1941	121	36, 347	127, 328	163, 675	3, 30
North Central:					
Illinois	190	417, 961	410, 235	828, 196	332, 32
Indiana	122	171, 408	194, 103	365, 511	170, 130
Iowa	60	82, 246	97, 479	179, 725	52, 12
Kansas	37	19,625	56, 148	75, 773	3,94
Michigan	170	530, 608	514, 320	1, 044, 928	410, 41
Minnesota	68	37, 503	104, 429	141, 932	28, 10
Missouri		68, 348	163, 735	232, 083	61, 59
Nebraska		3, 744	7,867	11,611	1,91
North Dakota	2	1, 103	687	1, 790	7
South Dakota		l)			
Ohio		445, 474	614, 359	1, 059, 833	537, 660
Wisconsin	109	239, 984	241, 125	481, 109	182, 594
Total: 1942	1, 104	2, 018, 004	2, 404, 487	4, 422, 491	1, 780, 88
1941	1, 108	2, 837, 408	2, 873, 312	5, 710, 720	2, 436, 96
Rocky Mountain:				4 2	
Arizona		9, 133	24, 065	33, 198	
Colorado		15, 221	62, 960	78, 181	33, 16
Idaho		778	3, 125	3, 903	11:
Montana		9, 420	7,980	17, 400	53
Nevada	2	4,049	4, 236	8, 285	19
New Mexico		( <b>)</b>			
Wyoming	1	200.070	1 100	3	04 64
Utah		32, 076	58, 100	90, 176	24, 648
Total: 1942		70, 679	160, 467	231, 146	58, 480
1941	64	70, 997	142, 468	213, 465	70, 42
Pacific Coast:					
California	126	88, 638	227, 483	316, 121	45, 86
Oregon	36	9, 360	28, 307	37, 667	6, 453
Washington	50	15, 906	54, 237	70, 143	4, 94
Total: 1942	212	113, 904	310, 027	423, 931	57, 260
1941		165, 014	253, 071	418, 085	63, 80
				0.054.501	1 4, 490, 513
Total United States: 1942		3, 936, 603 5, 004, 864	5, 117, 918 5, 559, 273	9, 054, 521 10, 564, 137	1 5, 388, 747
1941	4,198	0,004,004	0,000,210	TO, 002, 101	- 0,000,12

<sup>&</sup>lt;sup>1</sup> Includes some pig iron used in making direct castings.

Air furnaces.—Ferrous scrap and pig iron consumed in air furnaces in 1942 amounted to 1,696,880 tons—a 7-percent decline from 1941. The use of home scrap decreased 5 percent, of purchased scrap 10 percent, and pig iron 8 percent; the use of total scrap decreased 7 percent. Thus, equipment of this type used relatively more pig iron than purchased scrap in 1942. No air-furnace operators reported the exclusive use of scrap in 1942 or 1941.

Ohio led in the consumption of scrap in air furnaces in 1942, followed in order by Illinois, Pennsylvania, Indiana, Michigan, Wisconsin,

and New York.

Consumption of ferrous scrap and pig iron in air furnaces <sup>1</sup> in the United States in 1942, by districts and States, in short tons

District and State	Active plants re-			Scrap		
District and State	porting		Home	Purchased	Total	Pig iron
New England: Connecticut	7		27, 238	6, 136	33, 374	15, 018
Massachusetts New Hampshire Rhode Island	4	}	21, 153	8, 377	29, 530	16, 110
Total: 1942		Γ	48, 391 45, 134	14, 513 15, 215	62, 904 60, 349	31, 128 31, 198
Middle Atlantic: Delaware. New Jersey. New York. Pennsylvania.	2 12 25	}	15, 820 59, 490 107, 172	2, 417 16, 743 43, 483	18, 237 76, 233 150, 655	11, 044 35, 273 85, 027
Total: 19421941	40 41	-	182, 482 192, 951	62, 643 77, 996	245, 125 270, 947	131, 344 151, 761
Southeastern and Southwestern: West Virginia Texas		}	10, 857	5, 298	16, 155	6, 022
Total: 19421941			10, 857 11, 571	5, 298 6, 656	16, 155 18, 227	6, 022 6, 984
North Central: Illimois Indiana Michigan Iowa Minnesota. Missouri Ohio Wisconsin	10 8 1 1 1 1 21	}	225, 196 85, 766 12, 870 196, 903 60, 822	86, 805 34, 547 4, 048 86, 913 17, 481	312,001 120,313 16,918 283,816 78,303	145, 926 50, 200 10, 965 118, 322 56, 761
Total: 1942	68 70		581, 557 617, 965	229, 794 248, 234	811, 351 866, 199	382, 174 409, 912
Rocky Mountain and Pacific Coast: Colorado California		}	4, 891	1,018	5, 909	4, 768
Total: 1942	4 4		4, 891 4, 606	1, 018 1, 324	5, 909 5, 930	4, 768 4, 980
Total United States: 1942 1941	129 131		828, 178 872, 227	313, 266 349, 425	1, 141, 444 1, 221, 652	555, 436 604, 835

<sup>&</sup>lt;sup>1</sup> Includes 3 Brackelsberg furnaces—1 each in Indiana, Ohio, and Michigan.

Crucible and puddling furnaces.—Crucible and puddling furnaces, whose combined output of iron and steel is very small, consume only

minor quantities of ferrous raw materials.

Blast furnaces.—Ferrous scrap constitutes only a small proportion of the metal-bearing materials consumed in blast furnaces. Other materials used in 1942 were 104,055,422 tons of iron and manganiferous iron ores, 6,368,611 tons of cinder and scale, and 4,177,674 tons of flue dust. Total consumption of scrap in 1942, as reported by 73 plants operating blast furnaces, was 2,937,511 tons, a 1-percent increase over 1941. Of the 1942 total, 53 percent was home scrap and 47 percent purchased scrap.

The proportion of scrap used in blast furnaces decreased in 1942, amounting to 5.0 percent of the pig iron produced, compared with 5.3 percent in 1941 and 4.5 percent in 1940. Purchased scrap was equivalent to 2.3 percent of the pig iron produced in 1942, compared

with 2.4 percent in 1941 and 1.7 percent in 1940.

Consumption of ferrous scrap and pig iron in crucible and puddling furnaces in the United States in 1942, by districts and States, in short tons

	Active plants		Scrap				
District and State	report- ing	Home	Purchased	Total	Pig iron		
New England: Connecticut. Massachusetts New Hampshire	1 2 1	293	265	558	2		
Total: 1942	4 4	293 861	265 854	558 1, 715	2 6		
Middle Atlantic and Southeastern: New Jersey Kentucky Pennsylvania	2 1 11	} 121 5,730	4, 166 19, 475	4, 287 25, 205	15, 872 34, 084		
Total: 1942	14 13	5, 851 5, 518	23, 641 22, 964	29, 492 28, 482	49, 956 54, 225		
North Central and Southwestern: Ohio Oklahoma Wisconsin	1 1 1	} 69	9	78	98		
Total: 1942/	3 5	69 138	9 307	78 445	98 159		
Total United States: 1942	21 22	6, 213 6, 517	23, 915 24, 125	30, 128 30, 642	50, 056 54, 390		

Consumption of ferrous scrap in blast furnaces in the United States in 1942, by districts and States, in short tons

	Active plants re-		Scrap	
District and State	porting	Home	Purchased	Total
New England and Middle Atlantic: Massachusetts New York Pennsylvania	6	12, 671 39, 199 584, 796	13, 701 59, 427 448, 690	26, 372 98, 626 1, 033, 486
Total: 19421941	24 28	636, 666 617, 486	521, 818 433, 525	1, 158, 484 1, 051, 011
Southeastern: Alabama Kentucky Maryland Tennessee West Virginia	1 1 2	184, 614	57, 136 128, 503	241, 750 186, 815
Total: 1942	14	242, 926 248, 499	185, 639 212, 214	428, 565 460, 713
North Central: Illinois	3 5 2 18	135, 934 67, 159 54, 812 420, 563	52, 773 96, 897 55, 580 459, 537	188, 707 164, 056 110, 392 880, 100
Total: 19421941	33 36	678, 468 714, 552	664, 787 670, 874	1, 343, 255 1, 385, 426
Rocky Mountain: ColoradoUtah	1 1	6,852	355	7, 207
Total: 19421941		6, 852 7, 329	355 459	7, 207 7, 788
Total United States: 19421941		1, 564, 912 1, 587, 866	1, 372, 599 1, 317, 072	2, 937, 511 2, 904, 938

The relative position of the two States that are large consumers of scrap in blast furnaces was reversed in 1942. Pennsylvania became the principal consumer, using 17 percent more than Ohio, the second ranking State; in 1941, Ohio furnaces consumed 8 percent more than Pennsylvania furnaces.

#### CONSUMPTION IN FERRO-ALLOY PRODUCTION

Data covering the consumption of iron and steel scrap and pig iron in the production of ferro-alloys were assembled for the first time for 1942. The canvass showed that 318,188 tons of ferrous scrap and pig iron were used for this purpose during the year. Various types of furnaces were operated for the manufacture of ferro-alloys, such as blast, electric, and thermic-reduction.

Consumption of ferrous scrap and pig iron by ferro-alloy producers in the United States in 1942, by districts and States, in short tons

	Active				
District and State	plants re- porting	Home	Purchased	Total	Pig iron
Middle Atlantic: New York	5 3	30	74, 291	74, 321	
Pennsylvania	8	225 255	1, 442 75, 733	75, 988	
Southeastern: Alabama South Carolina Tennessee West Virginia	1 1 2 1	} 40	92, 811	92, 851	19
	5	40	92, 811	92, 851	19
North Central and Pacific Coast: Iowa	1	1			
Minnesota California Oregon	1 1	1, 235	120, 226	121, 461	
Ohio	4	9, 323	18, 546	27, 869	
	8	10, 558	138, 772	149, 330	
Total United States	21	10, 853	307, 316	318, 169	19

<sup>1</sup> Comparable data not obtained for 1941.

#### CONSUMPTION IN MISCELLANEOUS USES

As in ferro-alloy uses, data were gathered for the first time for 1942 showing the consumption of iron and steel scrap in such miscellaneous uses as rerolling, copper precipitation, flux in lead blast furnaces, and as a reducing agent in chemical processes. A total of 947,615 tons of ferrous scrap was reported used in these operations during 1942; no pig iron was reported consumed. Illinois was the largest consumer of scrap for miscellaneous purposes, followed by Pennsylvania and New Jersey.

Consumption of ferrous scrap in miscellaneous uses in the United States in 1942, by districts and States, in short tons

District and State	Active plants re-		Scrap	al distrib
District and State	porting	Home	Purchased	Total
New England:	*	7		
Massachusetts	2	} 112	12, 243	12, 355
New Hampshire	1	J 112	12, 240	12, 000
	3	112	12, 243	12, 355
Middle Atlantic:				
New Jersey	19	4, 460	109, 816	114, 276
New York	10	1, 123	76, 591	77, 714
Pennsylvania	21	8, 243	116, 873	125, 116
	50	13, 826	303, 280	317, 106
Southeastern:				
Alabama	5 1	2, 249	26, 531	28, 780
Maryland Virginia	2	684	55, 398	56, 082
West Virginia	2 2		33,333	,
Georgia Tennessee	2 1	367	13,064	13, 431
돌아난다. 하는 얼마를 보는 모든	13	3, 300	94, 993	98, 293
Southwestern:			-	
Oklahoma Texas	1 2	307	7, 999	8, 306
	3	307	7,999	8, 300
Tth Clanting.				
North Central: Illinois	10	2, 313	169, 853	172, 160
Indiana	6	19, 169	20, 334	39, 503
Nebraska	1	57	29, 199	29, 256
Wisconsin Michigan	$\begin{array}{c} 1 \\ 2 \\ 4 \end{array}$	1,952	3, 920	5, 872
Minnesota	3	309	411	720
Missouri	6	44	59, 413	59, 457
Ohio	10	765	85,005	85, 770
	42	24, 609	368, 135	392, 744
Rocky Mountain:				
Arizona	1	1		00.45
Nevada	1 2 2 3	65	22, 390	22, 45
New MexicoColorado	2	K		
Montana	3	3, 479	24,901	28, 380
Idaho	1 5	1,940	30, 912	32, 85
Utah				
	15	5, 484	78, 203	83, 68
Pacific Coast:	_	001	91 670	99 027
California Washington	7 4	601 2, 587	31, 672 264	32, 27 2, 85
	11	3, 188	31, 936	35, 12
Datal ITmitad Ctaton	137	50, 826	896, 789	947, 61
Total United States	137	00,820	990, 189	941, 01

<sup>1</sup> Comparable data not obtained for 1941.

## FOREIGN TRADE 5

Imports.—Imports of iron and steel scrap into the United States, which have never been very significant, totaled 101,337 short tons valued at \$1,352,055 in 1942, compared with 71,775 tons valued at \$730,844 in 1941. Of the 1942 total, 60,024 tons came from Canada, 19,658 from Cuba, 9,058 from the Panama Canal Zone, 3,959 from Curação (N. W. I.), 3,532 from Jamaica, 2,242 from British Guiana, and 2,864 from other countries. In addition, 26,972 short tons of tin-plate scrap were imported during 1942, largely from Canada, compared with 25,312 tons in 1941 and 18,609 tons in 1940.

Exports.—Ferrous scrap exports (all types) from the United States in 1942 totaled only 141,736 short tons valued at \$3,321,523. In 1941, 904,249 tons valued at \$15,973,863 was exported. The low exportation in 1942 was due to two principal factors. Export licensing established in 1940 restricting exports of all grades of scrap, except to Great Britain and countries of the Western Hemisphere, remained in effect through 1942; also, available shipping facilities were more needed for the transportation of finished war materials. ments in 1942 included 5,196 tons of tin-plate circles, waste-waste tin plate, and terne plate clippings valued at \$469,458. In 1941, exports of this type of scrap totaled 15,909 tons valued at \$1,109,217. following table shows the principal countries to which scrap was exported during the 5-year period 1938-42.

Ferrous scrap exported from the United States, 1938-42, by countries, in short tons

Country	1938	1939	1940	1941	1942
CanadaGermany	103, 283 258, 611	196, 556 18, 574	411, 571	314, 555	1
Italy Japan Netherlands Poland and Danzig	486, 883 1, 547, 617 231, 341	477, 004 2, 279, 315 60, 665	356, 859 1, 079, 141 389	324	(1)
United Kingdom Other countries	169, 625 433, 829 127, 233	173, 161 569, 288 240, 009	1, 100, 774 210, 549	539, 650 49, 720	
Total value	3, 358, 422 \$45, 829, 533	4, 014, 572 \$55, 911, 516	3, 159, 283 \$48, 314, 146	904, 249 \$15, 973, 863	141, 736 \$3, 321, 523

<sup>&</sup>lt;sup>1</sup> Figures not yet compiled on annual basis for individual countries.

#### WORLD ASPECTS

Statistics on the production of steel and pig iron in the world during 1942 are not available, as publication of information has been suspended in many of the countries involved. However, as this is a mechanized war, iron and steel are highly essential to the military and naval forces; therefore, world steel and pig-iron production undoubtedly increased considerably, and the demand for and use of iron and steel scrap was greater than in any previous year.

#### REVIEW BY COUNTRIES

Canada.—Steel production in Canada reached unprecedented levels in 1942, when the output of steel ingots and castings increased approximately 16 percent over the production in 1941, the previous record

Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

The state of the s

Steel ingots and castings produced during 1942 totaled 3.121.000 short tons, whereas production in 1941 amounted to 2,701,000 tons. The increase in Canadian blast-furnace capacity in 1942 was reflected in the record production of pig iron, which showed a larger percentage increment than did steel manufacture. Production of pig iron in 1942 totaled 1,975,000 tons, compared with the previous record of 1,528,000 tons established in 1941, an increase of more than 29 percent.6 In the record production of steel approximately 1,619,000 tons of pig iron and 1,833,000 tons of scrap were used, resulting in a ratio of 47 percent pig iron to 53 percent scrap, with the scrap charge containing 49 percent home scrap and 51 percent purchased scrap. Slightly more than 130,-000 tons of scrap was used in the manufacture of pig iron during 1942. The increased production of steel occasioned alarm as to the scrap supply, but with the large increase in pig-iron production augmented by the scrap obtained from ingots and semifinished steel imported into Canada, these fears were unfounded. Although the production of steel increased, no shortage of scrap occurred, and dealers as well as consumers were able to create stock piles large enough to satisfy requirements for several months in 1943.7

At the beginning of 1942, to provide a larger quantity of steel and metals for war industries, the Minister of Munitions and Supply issued orders curtailing the manufacture of civilian materials in which steel or metal was the principal component.8 At various times throughout the year these restrictions were extended to embrace additional items, including civilian automobiles, refrigerators, other electrical products,

and cast-iron and steel pipe.

The maximum price regulations covering scrap established in 1941 were extended to include British Columbia and the Maritime Provinces, placing prices for scrap throughout the entire Dominion of In addition, the Steel Controller Canada under strict control.9 undertook supervision of distribution of scrap produced by war plants and placed this material under allocation to consuming mills most urgently in need of scrap.10 Early in the year the government agreed to permit consumers to absorb freight cost in excess of the established maximum prices when the origin of the scrap was remote from the consuming plant; however, they were required to adhere to the ceiling price at the point of purchase." This action tended to stimulate collection of scrap in the western provinces, thereby augmenting supplies near the consuming areas. Former programs to collect scrap were intensified and in the last 6 months of the year were placed under direct control of the government, which provided for a more aggressive salvage campaign on a nationwide basis.<sup>12</sup> The Steel Controller also placed operators of automobile-wrecking yards under strict control, which required them to dispose of all wrecked cars within 90 days from the date the order was issued in March.13 During August the Department of Munitions and Supply issued an order stating that it would be illegal to retain possession of any scrap metal weighing 500

Department of Trade and Commerce, Monthly Report, Production of Iron and Steel in Canada,

<sup>Department of Trade and Commerce, available 1942.
American Metal Market, vol. 49, No. 246, Dec. 23, 1942, p. 7.
Steel, vol. 110, No. 1, Jan. 5, 1942, p. 383.
American Metal Market, vol. 49, No. 74, Apr. 18, 1942, p. 9.
The Iron Age, vol. 149, No. 13, Mar. 16, 1942, p. 129.
American Metal Market, vol. 49, No. 10, Jan. 15, 1942, p. 9.
Daily Metal Trade, vol. 32, No. 210, Oct. 27, 1942, p. 14.
Daily Metal Reporter, vol. 42, No. 55, Mar. 21, 1942, p. 11.</sup> 

pounds or more after September 15.14 The order included as scrap any machinery, structural steel, or other article containing iron and steel; it also provided for disposal within 20 days of any scrap metal obtained after the effective date. All these acts increased the flow of scrap material during the year, thereby creating supplies in excess of demands and providing ample inventories at the close of the year. Since exportation of iron and steel scrap from Canada ceased in 1939. except to the United Kingdom and nations of the Western Hemisphere,

exports have decreased considerably.

Germany.—Statistics on the production of steel and pig iron and on the consumption of scrap in Germany are not now available. ever, as a result of annexation and military occupancy of European countries, steel-ingot capacity is estimated to have been 53,800,000 short tons at the beginning of 1942, or 6 percent greater than it was on January 1, 1941. Nevertheless, steel production has been curtailed considerably by shortages of raw materials and transportation The shortage of alloy materials is greatest, which has difficulties. caused the German steel industry to reduce previously accumulated stock piles of alloying elements. Drives for scrap were intensified, and orders were issued for the confiscation of all unused iron and steel, including finished castings and spare parts.<sup>17</sup> In addition, authorities in charge of war economy established an immense drive in all occupied areas to obtain scrap from sources other than war material.<sup>18</sup>

The German iron and steel industry was organized into one association under the supervision of the Ministry of Economics, with control over the foundries, blast furnaces, and steel works as well as the ore trade and the large iron and steel merchants. This organization was given complete control over the entire industry, including

raw materials, production, imports and exports, and prices. 19

Japan.—Reserve accumulations of scrap held by Japan at the beginning of the year 1942 were estimated at approximately 10,000,000 short tons.<sup>20</sup> The request, made in 1941 by the Ministry of Commerce, that steel-manufacturing companies use a ratio of 70 percent pig iron and 30 percent scrap, had the effect of extending the supply of scrap so that it would last several years should ingot production be maintained at the full capacity of 7,200,000 tons each year.21 To augment the scrap supply, the Government extended salvage operations previously inaugurated by recovering sunken ships from Japanese waters and by investigation and exploitation of all possible sources.<sup>22</sup> raw materials were placed under better control, with pig-iron sales being centralized through a separate organization that would purchase the entire output of the principal producers and then sell it to steel mills and foundries at a uniform price.23

United Kingdom.—Scrap became a more significant factor in the manufacture of steel in the United Kingdom in 1942, especially since production facilities were expanded and operations increased to a degree never before attained. Imports of scrap from the United

<sup>14</sup> Daily Metal Trade, vol. 32, No. 163, Aug. 20, 1942, p. 16.

15 Steel, vol. 111, No. 1, July 6, 1942, p. 74.

16 American Metal Market, vol. 49, No. 233, Dec. 5, 1942, p. 1.

17 Daily Metal Trade, vol. 32, No. 165, Aug. 22, 1942, p. 14.

18 Daily Metal Reporter, vol. 42, No. 251, Dec. 31, 1942, p. 11.

19 The Iron Age, vol. 150, No. 5, July 30, 1942, p. 96.

20 The Iron Age, vol. 149, No. 4, Jan. 22, 1942, p. 73.


21 Foreign Commerce Weekly, vol. 4, No. 2, July 12, 1941, p. 14.

22 Daily Metal Trade, vol. 32, No. 133, July 9, 1942, p. 6.

23 Thon and Coal Trades Review (London), vol. 144, No. 3860, Feb. 20, 1942, p. 174.

States had been discontinued in September 1941, thereby disturbing normal operations; however, this was partly counteracted by the varying amounts of scrap obtainable from ingots and semifinished material imported under lend-lease agreements. As nearly all the scrap contained in buildings damaged by bombs had been salvaged in 1941, the Ministry of Works and Buildings undertook intensive nationwide drives for iron and steel scrap from other sources, including homes, farms, commercial premises, derelict properties, disused machinery, and pithead equipment.<sup>24</sup> The control of Iron and Steel (Scrap) Order 14, which was issued in 1941 by the British Ministry of Supply to completely control all buying and selling of scrap, was amended to provide higher prices for high-speed steel scrap and magnet scrap.<sup>25</sup> The Ministry of Works and Buildings issued an order designed to compel any person having more than 3 tons of scrap in his possession to sell it if required, thus making it possible to enforce compulsory liquidation of all substantial quantities of this essential raw material.26 Since transportation difficulties were anticipated and also to compensate for the lack of imports, a series of dumps throughout the country was established to provide a reserve supply of Also, issued by the Ministry of Works and Buildings was an order making the disclosure of scrap metal compulsory in Great Under this order, any metal that forms part of any unused. obsolete, or redundant building, structure, plant, or article is considered to be scrap.<sup>28</sup> In the meantime, the voluntary salvage drives underway yielded approximately 1,400,000 tons in 14 months.

<sup>American Metal Market, vol. 49, No. 25, Feb. 5, 1942, p. 8.
The Metal Bulletin (London), No. 2685, Apr. 17, 1942, p. 10.
Iron and Coal Trades Review, vol. 145, No. 3872, May 15, 1942, p. 127.
Iron and Coal Trades Review, vol. 145, No. 3876, June 12, 1942, p. 291.
American Metal Market, vol. 49, No. 202, Oct. 17, 1942, p. 7.</sup> 



# IRON ORE, PIG IRON, FERRO-ALLOYS, AND STEEL

By Norwood B. Melcher and Edward J. Langey 1

# SUMMARY OUTLINE

	Page	Pig iron—Continued.	Page
General features in 1942	569	Commercial quotations	599
Salient statistics	570	Foreign trade	. 600
Iron ore	573	Consumption	
Production and shipments	573	World production	603
Principal mines	576	Ferro-alloys	
Beneficiation	578	Production and shipments	603
Average value	579	Ferromanganese	604
Consumption	580	Spiegeleisen	608
Stocks at mines	. 581	Ferrosilicon	608
Stocks at consuming plants	. 581	Spiegeleisen Ferrosilicon Ferrophosphorus	60
Foreign trade		Ferrotungsten	. 608
Mining in Cuba	582	Ferrochromium	608
Review of Lake Superior district	. 583	Ferromolybdenum	608
Production and shipments	. 583	Molybdenum compounds	. 608
Analyses	584	Ferrovanadium	. 606
Stocks at Lake Erie ports	584	Silicomanganese	
Prices of Lake Superior ore	- 584	Manganese briquets	
Reserves Mining by States	- 584	Ferrotitanium	
Mining by States	586	Ferroboron	. 606
Employment at iron mines	592	Ferrocolumbium	. 606
World production		Zirconium-ferrosilicon	
Sponge iron		Foreign trade	
Pig iron	- 597	Steel	607
Production and shipments	597	General features	607
Value at blast furnaces	599		610

# **GENERAL FEATURES IN 1942**

Steel-industry production figures continued upward in 1942. Steel-making capacity increased 2 percent, while production of steel ingots and castings increased 4 percent and totaled 86,031,931 short tons—an all-time high. Pig-iron production totaled 59,077,593 tons, and usable iron-ore output (exclusive of ore containing 5 percent or more manganese) was 118,189,336 tons—both all-time records.

569

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Salient statistics of iron ore, pig iron, ferro-alloys, and steel in the United States, 1941-42

	1941-42		1	
		1941	1:	942
	Short tons	Value	Short tons	Value
Crude iron ore: Production by districts: Lake Superior. Southeastern. Northeastern. Western.	1 99, 921, 135 12, 810, 546 6, 284, 913 1, 629, 335	<b>(2)</b>	115, 773, 591 17, 132, 415 6, 940, 702 1, 863, 708	} (2)
	120, 645, 929	(2)	141, 710, 416	(2)
Production by mining methods: Open pit Underground	\$ 88, 971, 076 \$ 31, 674, 853	} (2)	{ 103, 269, 505 38, 440, 911	} (2)
	120, 645, 929	(2)	141, 710, 416	(2)
Production by types of ore:  Hematite Brown Magnetite Carbonate	987	(2)	125, 650, 342 8, 646, 791 7, 412, 137 1, 146	(2)
	120, 645, 929	(2)	141, 710, 416	(2)
Shipments Usable iron ore:	(2)	(2)	142, 010, 365	(2)
Production by districts:  Lake Superior Southeastern Northeastern Western Undistributed (byproduct ore)	1 88, 321, 332 9, 123, 408 4, 437, 521 1, 616, 468 (2)	(2)	101, 925, 624 10, 258, 335 3, 493, 847 1, 791, 358 720, 172	(2)
	103, 498, 729	(2)	118, 189, 336	(2)
Production by variety: Direct. Sinter. Concentrates. Byproduct ore (pyrite cinder and	<b>(2)</b>	(2)	91, 551, 205 3, 429, 898 22, 488, 061	(2)
sinter)	(4)	(4)	720, 172	J
	103, 498, 729	(2)	118, 189, 336	(2)
Shipments	<sup>5</sup> 104, 220, 473	* \$249, 705, 903 2, 40	118, 707, 133	\$279, 178, 751 2. 35
Average value per ton at mine	4, 023, 197 2, 625, 261 2, 136, 525	(2) 5, 347, 277 6, 212, 308	3, 770, 869 819, 084 2, 817, 235	2, 35 (2) 2, 142, 569 8, 114, 586
Production	55, 085, 446 55, 223, 641	1, 111, 811, 316 20, 13	59, 077, 593 59, 100, 601	(2) 1, 227, 389, 689 20, 77
Exports Ferro-allovs:	3, 675 578, 533	61, 130 15, 606, 692	110, 647	3, 144, 701
Production	1, 636, 073	(2)	1, 889, 409	(2)
Shipments: Ferromanganese Spiegeleisen Ferrosilicon Other ferro-alloys	619, 395 181, 177 661, 913 257, 300	69, 378, 004 5, 793, 481 34, 084, 428 95, 600, 706	659, 219 186, 163 707, 522 307, 383	82, 726, 298 5, 931, 728 39, 691, 636 129, 399, 523
Imports:	1, 719, 785	204, 856, 619	1, 860, 287	257, 749, 185
Ferromanganese Spiegeleisen Ferrosilicon	7, 032 4, 741 18, 261	557, 150 215, 108 750, 975	14, 772 1, 990 15, 211	1, 274, 749 95, 853 569, 134
Steel: Production:				
Open-hearth: Basic	73, 312, 851 1, 076, 768 5, 578, 071 2, 313 2, 869, 256	(2)	75, 183, 065 1, 318, 892 5, 553, 424 2, 010 3, 974, 540	(2)
Shipments to consuming industry	82, 839, 259 62, 484, 162	(2) (2)	86, 031, 931 60, 440, 000	(2) (2)

Includes a small quantity of ore from southern Wisconsin.
 Data not available.
 Some underground included with open pit in 1941.
 Undetermined—not included in total.
 Exclusive of ore for paint in 1941.

Most of the normal steel-consuming industries received less steel in 1942 than in 1941, owing to the very heavy demands for steel by industries engaged in direct war production. The automobile industry, normally the largest single consumer, ceased producing passenger cars in March, and output totaled only 206,274 units, compared with nearly 5 million in 1941; it was the largest industry to convert to war production. Shipbuilding activity increased phenomenally in 1942; deliveries of steel for shipbuilding soared from less than 3 million tons in 1941 to 9,425,000 tons in 1942. Miscellaneous industries and exports (which include arms production and Lend-Lease consignments) received the largest share (24.6 percent)




FIGURE 1.—Trends in production of iron ore and pig iron in the United States, 1880-1942.

of steel shipments in 1942, and a slight increase in shipments to the

construction industry was apparent during the year.

The annual steel-making capacity of the United States increased to a total of 90,293,000 tons of steel ingots and castings as of January 1, 1943, or 1,723,000 tons above the previous high level of 88,570,000 tons on January 1, 1942. Blast-furnace capacity increased from 60,394,000 tons on January 1, 1942, to 63,302,000 tons at the opening of 1943. The present expansion program for pig-iron- and steel-making capacity will be completed about January 1, 1944. At the completion of the program the United States will have the capacity to produce 97,340,000 tons of steel ingots and castings and 70,881,000 tons of pig iron.

During 1942 the most important development in Government regulation of the flow of steel for war production was the establishment of the Controlled Materials Plan, known as CMP. This plan, effective in the first quarter of 1943, is designed to maintain maximum

production of war products and essential civilian products within the limits of available materials and facilities. Its sponsors claimed that it established quantitative controls for a direct balancing of the demand for products with the supply of materials and facilities available for

their production.

A drop in employment was felt in the steel industry during 1942. The average number of men engaged in the industry (blast furnaces, steel works, and rolling mills) declined from 543,000 in December 1941 to 520,000 in December 1942. However, employment reached a maximum in June 1942, with a total of 549,000 employees. The average earnings per week in 1942 increased from \$39.26 in January to \$45.15 in December. Early in 1943, the War Manpower Com-




FIGURE 2.—Trendsin prices of iron ore, pig iron, finished steel, and steel scrap, 1890–1942. The prices of iron ore and pig iron are the averages, f. o. b. mines and furnaces, respectively, as reported to the Bureau of Mines; the price of finished steel is an average composite computed by American Metal Market; that of steel scrap is an average at Pittsburgh of No. 1 Heavy Melting, computed by Iron Age.

mission gave notice to the steel industry that unless mills are operating on a 48-hour week after July 1, 1943, no additional workers shall be hired for work therein without the approval of the War Manpower Commission. This order in effect will make a 48-hour work week mandatory. It is estimated that because of time-and-a-half pay for work over 40 hours, total wages will increase about 100 million dollars a year. However, about 50,000 fewer employees will be required under this program.

In July 1942 the National War Labor Board granted 157,000 employees of four steel companies (Bethlehem Steel Corporation, Inland Steel Co., Republic Steel Corporation, and Youngstown Sheet

& Tube Co.) an increase in wages of 5½ cents per hour. This action brought about adoption of the Little Steel Formula, designed to guide the settlement of wage disputes in other industries. The program provides for a 15-percent increase from the wage level of January 1, 1941. Dr. George W. Taylor, representing the public on the Board, in reviewing the program gave the following principle as a guide in evaluating claims for wage increases <sup>2</sup>:

For the period from January 1, 1941, to May 1942, which followed a long period of relative stability, the cost of living increased by about 15 percent. If any group of workers averaged less than a 15-percent increase, the hourly wage rate during, or immediately preceding, or following this period, their established peacetime standard has been broken. If any group of workers averaged a 15-percent wage increase or more, their established peacetime standard has been preserved.

This formula eventually affected almost every wage earner in the steel industry and most salaried workers as well, with increases retroactive to February 1942. Application of the formula led to wage advances in the automobile industry, whose case was then pending, and to increases in other industries.

#### IRON ORE

#### PRODUCTION AND SHIPMENTS

The enormous demand for iron ore by a wartime steel industry resulted in a record year in domestic iron mining. United States iron mines produced 141,710,416 short tons of crude ore during 1942, and shipments totaled 142,010,365 tons. Of this latter quantity, 49,936,613 tons were shipped to beneficiation plants and 92,073,752 tons direct to consumers. A total of 25,917,959 tons of beneficiated ore were produced at milling plants, in addition to 720,172 short tons of byproduct cinder and sinter from the pyrite industry. all, 118,189,336 short tons of usable ore were produced in 1942. Output in 1942 came from 252 mines, of which 35 mined over 1,000,000 tons of crude ore each. Minnesota, with 82,809,939 tons, supplied 70 percent of the usable ore, and Michigan, with 17,499,060 tons or 15 percent, was the second-largest producer. These two States and Wisconsin (1,682,897 tons or 1 percent) constitute the Lake Superior region, which supplied 86 percent of the domestic output. About three-fourths of the iron ore mined in 1942 came from open-pit mines.

Shipments of usable ore from mines totaled 118,707,133 short tons in 1942. Of this quantity, 91,972,925 tons or 77 percent was directly shipping ore for iron and steel furnaces. Total shipments also include 74,036 tons for cement manufacture, 29,424 tons for paint, and 34,842 tons for miscellaneous uses. Shipments and values of byproduct ore for iron- and steel-furnace use are included for the first time in 1942. These shipments totaled 755,844 tons in 1942 valued at \$3,237,511.

<sup>&</sup>lt;sup>2</sup> Taylor, George W., "Terminal" for Present Ratio of Wages, Prices Sought by Board: Steel, vol. 11, No. 3, July 20, 1942, pp. 43-44.

## Crude iron ore mined in the United States in 1942, by States and varieties, in short tons

[Exclusive of ore containing 5 percent or more manganese]

State	Number of mines	Hematite	Brown ore	Magnetite	Carbo- nate	Total
AlabamaArizonaCalifornia	1 47 1 5	8, 678, 345 386 2 91, 525	6, 930, 768	2 14, 995		15, 609, 113 386 106, 520
GeorgiaMichigan	1 20 44	5, 128 17, 499, 060	1, 501, 137	- 11, 000		1, 506, 265 17, 499, 060
Minnesota Missouri New Jersey	101 1 4 4	96, 591, 634 6, 935	101, 956 61, 173	1, 494, 853		96, 693, 590 68, 108 1, 494, 853
New Mexico New York Pennsylvania	1 8 5 2	18, 631 2, 183		88, 675 5, 442, 520	{	107, 306
Texas Virginia Utah	1 2		<b>51,</b> 757	359, 558		51,757
Washington Wisconsin Wyoming	3 2 1	1, 748 1, 682, 897 1, 071, 870		11, 536		359, 558 13, 284 1, 682, 897 1, 071, 870
Total: 1942 1941	1 252 1 276	2 125, 650, 342 (3)	8, 646, 791 (3)	<sup>2</sup> 7, 412, 137	1, 146 987	141, 710, 416 120, 645, 929

Excludes an undetermined number of small pits. Output of these pits included in tonnage given.
 Small quantity of magnetite included with hematite.
 Break-down by varieties not available for 1941.

The output of manganese-bearing ore containing 5 percent or more manganese is not considered in this chapter.

Crude iron ore mined in the United States, 1941-42, by States and mining methods, in short tons

		1941			1942	
State	Open pit	Under- ground	Total	Open pit	Under- ground	Total
Alabama	3, 775, 851	7, 767, 665	11, 543, 516	7, 044, 822 386	8, 564, 291	15, 609, 113 386
California	60, 293 99		60, 293 99	105, 473	1,047	106, 520
Georgia	1, 264, 978 1, 911, 140 76, 632, 384	1,624 14,520,595 5,248,435	1, 266, 602 16, 431, 735 81, 880, 819	1,506,265 1,101,359 91,214,064	16, 397, 701 5, 479, 526	1, 506, 265 17, 499, 060 96, 693, 590
Mississippi Missouri Nevada	57 19,453 241	1,438	57 20, 891 241	63, 568	4, 540	68, 108
New Jersey New Mexico New York		1, 429, 556	1, 429, 556	104, 882	1, 494, 853 2, 424	1, 494, 853 107, 306
Pennsylvania South Dakota	14, 855, 258	(1)	4, 855, 258	1, 705, 835	3,740,014	5, 445, 849
Virginia Texas Oklahoma	34, 846		34, 846	<b>{</b> } 51,757		51, 757
Utah Washington	397, 607 11, 200	474	397, 607 11, 674	359, 558 11, 536	1,748	359, 558 13, 284
Wisconsin Wyoming	4, 480 3, 189	1,604,101 1,100,965	1, 608, 581 1, 104, 154		1,682,897 1,071,870	1, 682, 897 1, 071, 870
	88, 971, 076	31, 674, 853	120, 645, 929	103, 269, 505	38, 440, 911	141, 710, 416

<sup>&</sup>lt;sup>1</sup> Underground included with open pit.

# Usable iron ore produced in the United States in 1942, by States and types of product, in short tons

[Exclusive of ore containing 5 percent or more manganese]

State	Direct shipping ore	Sinter 1	Concen- trates	Pyrite cinder and sinter	Total	Iron content, natural (percent)
AlabamaArizona	7, 112, 171 386	1, 203, 792	1, 596, 635		9, 912, 598 386	36. 77 58. 00
CaliforniaGeorgia	106, 520 5, 128		329, 214		106, 520 334, 342 17, 499, 060	56.30 47.28 51.68
Michigan Minnesota Missouri	17, 499, 060 63, 271, 187 53, 091	301, 434	19, 237, 318 6, 089		82, 809, 939 59, 180	52.11 49.74
New Jersey New Mexico New York	107, 323	1 004 670	569, 214		676, 537 107, 306 2, 817, 310	62.89 54.85 65.95
Pennsylvania Texas Virginia	161, 171 253	1, 924, 672	731, 467 18, 124		18, 377	55, 19 52, 51 37, 41
Utah Washington	359, 558 13, 284				359, 558 13, 284 1, 682, 897	53. 49 61. 33 52. 65
Wisconsin Wyoming	1, 682, 897 1, 071, 870				1, 071, 870	49.89
Byproduct ore: 2	91, 551, 205	3, 429, 898	22, 488, 061		117, 469, 164	51.00
Delaware Michigan Pennsylvania				720, 172	720, 172	61.89 65.91 62.66
TennesseeVirginia				,112	.=0,=	67. 20 54. 10
				720, 172	720, 172	63.74
Grand total	91, 551, 205	3, 429, 898	22, 488, 061	720, 172	118, 189, 336	51.08

Exclusive of sinter produced at consuming plants.
 Obtained from pyrite treated in, but not necessarily mined in, States indicated.

# Crude iron ore mined in the United States in 1942, by mining districts and varieties, in short tons

# [Exclusive of ore containing 5 percent or more manganese]

District	Hematite	Brown ore	Magnetite	Carbonate	Total
Lake Superior 1  Birmingham  Chattanooga  Adirondack and Cornwall	115, 773, 591 8, 678, 263 5, 210	2, 665, 924 2, 576, 970	5, 442, 520		115, 773, 59 11, 344, 18' 2, 582, 18 5, 442, 52
Northern New JerseyOther districts	2 1, 193, 278	3, 403, 897	1, 494, 853 2 474, 764	1, 146	1, 494, 85 5, 073, 08
	2 125, 650, 342	8, 646, 791	2 7, 412, 137	1, 146	141, 710, 410

Includes only those mines in Minnesota that are in the true Lake Superior district.
 Small quantity of magnetite included with hematite.

Shipments of usable iron ore in the United States in 1942, by States and uses, in short tons

[Exclusive of ore containing 5 percent or more manganese]

		Iron ar	ıd steel					T	otal
State	Direct shipping ore	Sinter 1	Concentrates	Pyrite cinder and sinter	Ce- ment	Paint	Mis- cella- neous	Short tons	Value
Alabama	7, 109, 814 386	1, 203, 792	1, 592, 957						\$19, 034, 75
California Georgia Michigan	20, 265 4, 960		329, 214				14, 306	334, 174	239, 42 722, 01
Minnesota Missouri	53, 636	301, 434	19, 239, 922			397		18, 065, 011 82, 728, 985 62, 247	45, 599, 53 179, 752, 23 177, 58
New Jersey New Mexico New York	107, 156		550, 828		2, 850		104	675, 763 107, 306	3, 672, 75 299, 09
Pennsylvania Texas Virginia	152, 567 22	1, 928, 640	686, 049			2, 687 11, 515		2, 769, 943 19, 445	, , , , , ,
Utah Washington					1, 737			358, 214 13, 273	(2) (2)
Wisconsin	1, 734, 089 1, 071, 870							1, 734, 089 1, 071, 870	3, 936, 596 (2) 3 5, 756, 62
Byproduct ore:4 Delaware	91, 972, 925	3, 433, 866	22, 406, 196		74, 036	29, 424	34, 842	117, 951, 289	
Michigan Pennsylvania Tennessee Virginia	}			755, 844				755, 844	3, 237, 51
Grand total	91, 972, 925	3, 433, 866	22, 406, 196	755, 844	74, 036	29, 424	34, 842	118, 707, 133	279 178 751

# Crude iron ore shipped from mines in the United States in 1942, by States and disposition, in short tons

	State	Direct to con- sumers	To beneficia- tion plants	Total
California Georgia Michigan Minnesota Missouri New Jersey New Mexico New York Pennsylvania Texas Virginia Utah Washington Wissonsin		7, 109, 814 386 104, 020 4, 960 18, 065, 011 63, 187, 621 107, 156 107, 306 154, 750 253 358, 214 13, 273 1, 734, 089 1, 071, 870 92, 073, 752	8, 505, 422 1, 501, 137 33, 142, 184 14, 029 1, 397, 425 5, 324, 912 51, 504 49, 936, 613	15, 615, 23 38 104, 02 1, 506, 09 18, 065, 01 96, 329, 81 107, 30 5, 479, 66: 51, 75: 358, 21: 13, 27: 1, 734, 088 1, 071, 876

# PRINCIPAL MINES

The size of a mine is determined by the quantity of crude ore excavated. Hence, mines producing low-grade ores, which require concentration, will be comparable in size to mines producing direct shipping ores. A total of 35 mines, yielding more than 1,000,000

Exclusive of sinter produced at consuming plants.
 Value included with "Undistributed."
 Includes values for States entered as "a".
 Obtained from pyrite treated in, but not necessarily mined in, States indicated.

short tons of crude ore each, produced 62 percent of the entire output in 1942. Of these producers, 25 were in Minnesota, 4 were in Alabama, 2 in New York, and 1 each in Michigan, Pennsylvania, Wisconsin, and Wyoming; 22 were open-pit operations, 9 were underground operations, and 4 were combination mines. Except for 3 mines that produced magnetite, all the million-ton mines produced hematite.

Iron-ore mines in the United States in 1942, by size of crude output

Name of mine	State	Nearest town	Range or dis- trict	Mining method	Short ton
Hull - Rust - Burt - Sellers	3.5				
Penobscot	Minnesota	Hibbing	Mesabi	Open pit	24, 121, 68 5, 727, 10 4, 531, 69 4, 172, 41 2, 627, 70 2, 598, 77 2, 184, 21
Hill Annex	do	Calumet	do	do	5, 727, 10
Hill Annex Mahoning Adams Spruce	00	Hibbing Eveleth Nashwauk Marble Chisholm	ao	Combined	4, 551, 69
Adams Spruce	do	Eveleth	ao	Combined	4, 172, 41
Kevin	do	Nashwauk	do	Open pit	2,027,70
Hill Trumbull Frazer D'Autremont	đo	Chiabolm	do	do	2, 550, 77
Alpena (stockpile)	do	Virginio	do	do	2, 056, 70
Muscoda	Alabama	Chisholm Virginia Bessemer do Hibbing Coleraine Taconite Chisholm Eveleth Hibbing Marble Cooley Coleraine	Birmingham	Underground	1, 972, 85
Wenonah	do	do	do	do	1, 908, 44
Y	do Minnesota	Hibbing	Mesabi	Open pit	1, 840, 33
Monwigon	do	Coleraine	do	do	1, 836, 12
Holmon-Brown	do	Taconite	do	do	1, 820, 09
formard-Burt-(Hen		Chisholm	do	do	1, 820, 03
Hull-Nelson	do	Eveleth	do	do	1, 727, 62
Mounia	do	Hibbing	do	Combined	1, 676, 04
Amoturne	ao	Marble	do	Open pit	1, 645, 39
Harrison	do	Cooley	do	do	1, 587, 11 1, 550, 12
Canisteo	ao	Coleraine Bessemer	Dii	Tradoressand	1 400 40
shkooda	Alabama	Bessemer	Mesabi	Combined	1,400,40
Bennett	Minnesota do	Keewatin Coleraine	MTGSBD1	Open pit	1 320 00
Danube	Alahama	Bessemer	Rirmingham	Open pit Undergrounddo	1, 450, 46 1, 409, 76 1, 329, 09 1, 279, 21 1, 252, 48 1, 239, 49
Woodward No. 3	Alabama Wisconsin		Gogehic	do	1, 252, 48
Montreal	Michigan	Negginee	Marquette	do	1, 239, 49
Negaunee Rouchleau (stockpile)	Minnesota	Montreal Negaunee Virginia Nashwauk do Calumet	Mesabi	Open pit	1, 175, 95 1, 165, 43 1, 146, 00
Howking	do	Nashwank	do	do	1, 165, 43
A roonne	do	do	do	do	1, 146, 00
Majoroa	QO:I	Calumet	do	do	1, 135, 48 1, 132, 98
Majorca Susquehanna	do Wyoming	Hibbing	do	do	1, 132, 98
Sunrise	Wyoming	Sunrise	Hartville	Underground _	1,071,87
Schley	Minnesota	Gilbert	Mesabi	Open pit	1,015,25
Surrise Schley Maas	Michigan	Calumet Hibbing Sunrise Gilbert Negaunee Russellville Nashwauk	Marquette	Underground -	988, 28
Russellville Nos. 5 and 12-	Alabama	Russellville	Russellville	Open pit	976, 72 949, 55
Galbraith	Minnesota	Nashwauk	Mesabido	do	948, 51
Corsica	do	Elcor	do	Combined	929, 34
Webb	New Jersey	Hibbing Dover	New Jersey	Underground.	921, 06
Scrub Oaks Penn Group	Michigan	Vulcan	Menominee	do	
Giles	Alabama	Woodstock	Birmingham	Open pit	879, 82 874, 72 847, 96 809, 31 801, 25 799, 15 791, 24 771, 96 763, 55 762, 39 751, 44 745, 55
Zonith	Minnesota	Ely	Vermilion	Open pit Undeground	847, 96
Zenith Raimund Nos. 1 and 2	Alabama	Bessemer	Birmingham	do	809, 31
Warren	Minnesota	Hibbing	Mesabi	Open pit	801, 25
Warren Cliffs Shaft	Michigan	Ishpeming	Marquette	Underground .	799, 15
Wabigoni	Minnesota	Buhl Wakefield	Mesabi	Open pit	791, 24
Plvmouth	Michigan	Wakefield	Gogebic	do	771,96
AAbama	do	Negaunee	Marquette	Underground .	763, 50
Barbara Geneva-West Davis Grant	Minnesota Michigan	Greenway Ironwood	Mesabi	Open pit	702, 38
deneva-West Davis		Ironwood	Gogebic	Underground .	701, 14
Grant	Minnesota	Buhl	Mesabi Menominee	Open pit	745, 55 727, 22 725, 98
Hiawatha Nos. I and 2i	Michigan	Stambaugh Chisholm	Menominee	Underground	725 00
Godfrey Cornwall	Minnesota	Chisholm Cornwall Lyon Mountain Mineville	Comprell	Combined	120, 80
Cornwall	Pennsylvania. New York	Comwaii	Adirondook	Underground	5, 011, 67
Chateaugay Harmony-Old Bed	New York	Lyon Mountain	Adiiondack	Onderground .	[ 0,011,0
					,
Output of 55 mines produc	ing more than 70	0 000 tone each			105, 014, 3
					5, 851, 9
Output of 10 mines product	ing 500,000 to 600	0.000 tons each			F F00 0
Justinit of 14 mines produc	ing 400,000 to 500	.000 tons each			6, 412, 9
output of 16 mines produc	ing 300,000 to 400	.000 tons each			5, 502, 0
output of 21 mines produc	ing 200,000 to 300	.000 tons each			4, 974, 74
Output of 33 mines produe	ing 100,000 to 200	,000 tons each			4, 659, 6
Output of 24 mines produc	ing 50,000 to 100.	000 tons each			1, 691, 8
Output of 10 mines produc Output of 14 mines produc Output of 16 mines produc Output of 21 mines produc Output of 33 mines produc Output of 24 mines produc Output of 70 mines produc	ing less than 50,0	000 tons each			891,80
Output of 70 mines product Output from reprocessed to	ailings (3 plants)				1, 179, 90
Grand total of Unite					141, 710, 4

<sup>1</sup> Excludes an undetermined number of small pits. The output of these pits is included in the total given.

#### BENEFICIATION

Iron ore is concentrated by washing, jigging, and magnetic and high-density separation to remove objectionable impurities, thereby improving the grade of the ore. Fine ores are agglomerated or sintered into lumps, which are desirable in blast and steel furnaces because of their porous character and their improved grade and structure. Sintering likewise has the beneficial effect of reducing the sulfur and moisture content. At many mines the ore is crushed and screened to improve its physical characteristics, but ore known to be so improved is not included in the statistics on beneficiated ore.

In 1942 a total of 25,917,959 short tons of beneficiated ore was produced from 49,936,613 tons of crude ore. Beneficiation of iron ore was reported at 120 miles in 9 States in 1942, compared with 112 mines in 8 States in 1941. Beneficiated ore shipped from domestic mines in 1942 increased 21 percent over 1941; concentrates comprised 19 per-

cent and sinter 3 percent of total usable ore shipments.

Beneficiation of crude iron ore in the Lake Superior district (all in Minnesota) began in 1907, when 10,994 short tons of concentrates were shipped from the experimental washing plant of the Oliver Iron Mining Co. on the Mesabi range.<sup>3</sup> From that date, the construction of additional washing, drying, jigging, magnetic concentrating, sintering, and high-density plants in Minnesota increased the proportion of beneficiated-ore shipments to total shipments from 0.03 percent in 1907 to 24 percent in 1942. The quantity of crude ore beneficiated in 1942 totaled 33,142,184 short tons and the beneficiated ore recovered 19,538,752 tons—a ratio of 1.696:1. In 1941 the crude ore treated totaled 28,774,481 short tons and the beneficiated ore recovered therefrom 16,940,412 tons—a ratio of 1.699:1. During 1942, E. W. Davis, Mines Experimental Station, University of Minnesota. and G. W. Hewitt, 5 Wheeling Steel Corporation, urged the construction of additional concentrating plants to beneficiate the magnetic taconite ore at the eastern end of the Mesabi range, to conserve the reserves of Mesabi open-pit direct shipping ores. Davis states that the magnetic taconite may be treated by a process similar to that now in use by the Republic Steel Corporation in New York State. The process consists of crushing the crude ore to a fine size, extracting the iron oxide from it magnetically, and then agglomerating the concentrate. The sintered taconite concentrate would average 62 to 65 percent iron.

The Universal-Atlas Portland Cement Co., Universal, Pa., and the Buffalo Sintering Corporation, Buffalo, N. Y., beneficiated Lake ores. The nodulized ore produced at Universal was used for charge ore in the open hearth, and the sinter produced at Buffalo was consumed in both blast and open-hearth furnaces. Production from these plants is not included in usable ore statistics, as the tonnage has been ac-

counted for in mine shipments.

<sup>&</sup>lt;sup>3</sup> Craig, John J., Shipments of Concentrated Iron Ore from Minnesota at New Peak in 1941: Skillings Mining Review, vol. 30, No. 47, March 14, 1942, Duluth, Minn., pp. 1, 2, and 6.

<sup>4</sup> Davis, E. W., Lake Superior Iron Ore and the War Emergency: Blast Furnace and Steel Plant, vol. 30, No. 12, December 1942, pp. 1364-1368; vol. 31, No. 2, February 1943, pp. 211-216.

<sup>5</sup> Hewitt, G. W., Future Possibilities of Mesabi Magnetic Sinter: Blast Furnace and Steel Plant, vol. 30, No. 7, July 1942, pp. 753-754.

Iron ore shipped from mines in the United States, 1925-29 (average) and 1938-42, in short tons, and percentage of beneficiated ore compared to total shipped

[Exclusive of ore containing 5 percent or more manganese and of ore sold for paint 1]

Year	Benefici- ated	Total	Proportion of benefici- ated to total (per- cent)	Year	Benefici- ated	Total	Proportion of benefici- ated to total (per- cent)
1925-29 (ave.)	9, 692, 021	74, 700, 781	13. 0	1940	14, 476, 830	84, 221, 854	17. 2
1938	5, 416, 807	29, 602, 619	18. 3	1941	21, 701, 254	104, 220, 473	20. 8
1939	10, 556, 906	61, 406, 352	17. 2	1942	1 25,877, 538	1 117,951, 289	21. 9

<sup>1</sup> Includes ore for paint in 1942.

#### AVERAGE VALUE

The average value per short ton of usable iron ore at the mine was

\$2.35 in 1942, compared with \$2.40 in 1941.

The accompanying table gives the average value at the mines of the different classes of iron ore in 1942 for each of the producing States or groups of States, except when there are fewer than three shippers of a certain class of ore in a State and permission was not given to publish the value. These data are taken directly from statements of producers and probably represent the commercial selling prices only approximately, as not all reports are comparable. Some evidently include mining costs only; others contain, in addition, the cost of selling and insuring the ore; others include an allowance for a sinking fund; and still others comprise only costs charged against blast furnaces. None of the reports, however, is supposed to include freight charges.

Average value per short ton of usable iron ore at mines in the United States in 1942 [Exclusive of ore containing 5 percent or more manganese]

						**		
	Direct			C	oncentra	tes '		Pyrite
State	Hema- tite	Brown ore	Magne- tite	Hema- tite	Brown ore	Magne- tite	Sinter	cinder and sinter
Alabama			(1)	(1)	\$2. 23		(1)	
Georgia Michigan Minnesota	2. 52 2. 14			\$2.15	2.14 (1) (1)		\$2. 23	
Missouri New Jersey New Mexico New York	3.86	(1)	(1) \$2.56		(1)	\$5. 26		
New 101k Pennsylvania Wisconsin Other 2	2. 27 4. 02	(1)	(1) (1) 		(1)	4.08	6. 57	
Average, all StatesByproduct ore:	2. 24	\$2.66	4. 52	2. 17	2. 36	4. 62	4. 10	
Delaware Michigan Pennsylvania Tennessee Virginia	}					·		\$4. 2

Less than 3 producers; permission to publish not given, therefore value may not be shown.
 Includes Arizona, Texas, Utah, Virginia, Washington, and Wyoming.
 Obtained from pyrite treated in, but not necessarily mined in, States indicated.

#### CONSUMPTION

The production of 59,077,593 short tons of pig iron in 1942 required 104,055,422 tons of iron ore and manganiferous iron ore, 6,368,611 tons of mill cinder and roll scale, and 1,372,599 tons of purchased scrap, an average of 1.892 tons of metalliferous materials (exclusive of home

scrap and flue dust) per ton of pig iron made.

Most of the iron ore used in Alabama furnaces in 1942 was hematite from mines in Jefferson County, but small quantities of hematite from Cherokee and Etowah Counties and Walker County, Ga., were also employed. In addition, brown ore, iron sinter, pyrite ash, imported ore, and manganese-bearing ores were consumed. The brown ore originated chiefly in mines of the Birmingham and Russellville districts, Ala., and the Chattanooga district, Ga. The manganese-bearing ores came from Arkansas, Georgia, Tennessee, Virginia, and Cuba. Because of the low-grade ore used in Alabama, the furnaces in this State use more ore per ton of pig iron than any other district in the United States. During 1942 Alabama furnaces consumed an average of 2.537 tons of metalliferous materials per ton of pig produced.

Iron ore and other metallic materials consumed and pig iron produced in 1942, by States, in short tons

	Metal	liferous ma	terials con		Materials consumed per ton of pig iron made				
	Iron and n erous ir		Cinder, scale,		Pig iron produced		Cinder, scale, and		
	Domestic	Foreign	and pur- chased scrap	Total		Ores	pur- chased scrap	Total	
Alabama Illinois Indiana Kentucky Maryland Michigan Minnesota New York Ohio Pennsylvania	10, 206, 796 10, 398, 886 11, 383, 956 778, 100 3, 410, 606 2, 918, 514 644, 566 7, 255, 202 22, 135, 165 29, 623, 693	6, 133 726, 501 23, 861 94, 599 25, 650	141, 424 462, 668 821, 562 45, 587 551, 074 124, 309 64, 727 362, 582 1, 689, 900 3, 327, 035	10, 354, 353 10, 861, 554 12, 205, 518 823, 687 4, 688, 181 3, 066, 684 709, 293 7, 712, 383 23, 825, 065 32, 976, 378	4, 081, 710 5, 850, 070 6, 430, 820 457, 124 2, 490, 571 1, 683, 414 373, 492 4, 040, 756 13, 140, 362 18, 064, 888	2. 502 1. 778 1. 770 1. 702 1. 661 1. 748 1. 726 1. 819 1. 684 1. 641	0. 035 . 079 . 128 . 100 . 221 . 074 . 173 . 090 . 129 . 184	2. 537 1. 857 1. 898 1. 802 1. 882 1. 899 1. 813 1. 825	
West Virginia Undistributed 1	2, 465, 576 1, 933, 438	24, 180	101, 492 48, 850	2, 567, 068 2, 006, 468	1, 408, 993 1, 055, 393	1. 750 1. 855	.072	1. 822 1. 901	
	103, 154, 498	900, 924	7, 741, 210	111, 796, 632	59, 077, 593	1.761	. 131	1. 892	

<sup>&</sup>lt;sup>1</sup> Includes California, Colorado, Massachusetts, Tennessee, and Utah.

Maryland furnaces consumed chiefly domestic ore in 1942, in addition to ores from Africa, Brazil, Chile, Cuba, and India. These furnaces used an average of 1.661 tons of ore per ton of pig iron; however, they consumed proportionately more cinder, scale, and scrap than those in any other State.

Blast furnaces in Illinois, Indiana, Kentucky, Michigan, Minnesota, and West Virginia handled Lake Superior iron ore and manganiferous iron ore almost exclusively. Kentucky furnaces had the lowest con-

sumption of metal-bearing material per ton of iron.

In New York the furnaces in the Buffalo district used ore chiefly from the Lake Superior district, magnetite from New York, and some manganese ore from Cuba, and the furnace at Troy consumed magnetite from the Chateaugay mine at Lyon Mountain, N. Y.

The state of the s

Blast furnaces in Ohio consumed magnetite from New York in

addition to ore from the Lake Superior district.

Virtually all the ore consumed in western Pennsylvania furnaces came from the Lake Superior district. Those in the eastern part of the State used some Lake ore; magnetite ores from Pennsylvania, New Jersey, and New York; and some ore from Africa, Australia, Chile, Cuba, and Sweden.

The Pueblo (Colo.) blast furnaces consumed hematite from the Sunrise mine in Wyoming, hematite and magnetite from New Mexico, and manganese-bearing ores, chiefly from Colorado, New Mexico, and

California.

The Provo (Utah) furnace treated semialtered magnetite from the Iron Mountain mine near Cedar City, Utah, manganese tailings from Montana, and manganese-bearing ores from Nevada, Texas, and Utah.

Foreign iron and manganiferous iron ore consumed in the manufacture of pig iron in the United States, 1941-42, by sources of ore, in short tons

1941	1942	Source	1941	1942
14,775 2,265 17,883 202,809 1,907,980 232,848	4, 871 790 9, 173 114, 906 662, 420 77, 368 1, 573	Newfoundland Palestine Spain Sweden Source not stated	554 9, 496 	24, 180 2, 721 990 1, 932 900, 924
	14,775 2,265 17,883 202,809 1,907,980	14, 775 4, 871 2, 265 790 17, 883 9, 173 202, 809 114, 906 1, 907, 980 662, 420 232, 848 77, 368	14,775 4,871 Newfoundland Palestine 202,809 114,906 Sweden 1,907,980 662,420 Source not stated 232,848 77.368	14, 775

#### STOCKS AT MINES

Stocks of usable iron ore at mines totaled 3,770,869 tons at the end of 1942. In addition, 594,751 tons of pyrite cinder and sinter were in stock at plants that produce these byproducts for consumption in iron and steel furnaces. About 90 percent of United States mine stocks were in Michigan and Minnesota.

Stocks of usable iron ore at mines, December 31, 1941-42, by States, in short tons

State	1941	1942	State	1941	1942
Alabama	32, 136 67	33, 048 2, 500	New York Pennsylvania Texas	30, 947 90, 733 7, 683	61, 977 14, 354 6, 615
Georgia Michigan Minnesota	2, 172, 192 1, 467, 745	168 1,909,968 1,493,331	UtahVirginiaWisconsin	560 3, 456 213, 127	1, 344 4, 379 184, 144
Missouri New Jersey	2, 790 1, 761	1, 620 57, 421		4, 023, 197	3,770,869

#### STOCKS AT CONSUMING PLANTS

Stocks of iron ore at consuming plants totaled 45,658,562 short tons on December 31, 1942, compared with 40,509,863 tons on December 31, 1941. This large increase was made possible by a favorable shipping season, which enabled shipments to exceed demand. Despite the late opening of the 1943 shipping season, it is believed that stocks at consuming plants at the end of the year will suffice to meet demands until the opening of the 1944 shipping season.

#### FOREIGN TRADE

Imports of iron ore in 1942 decreased tremendously from 1941 owing to the crucial shipping problem. Because of enemy submarine activity, shipments from Chile, which had long been the largest supplier of foreign ore, were suspended in 1942.

Iron ore imported for consumption in the United States, 1940-42, by countries, in short tons

Country	19	940	19	41	1942		
	Short tons	Value	Short tons	Value	Short tons	Value	
Brazil British West Africa	111, 065 8, 053	\$460, 669 32, 775	133, 134	\$479, 122	53, 312	\$188, 908	
Canada <sup>1</sup> Chile Cuba Iran	1 248, 468 1, 884, 512 246, 011 4, 088	1 1, 056, 381 3, 028, 699 436, 515 85, 733	1 313, 864 1, 888, 074 201, 699	1 1, 182, 566 3, 064, 838 359, 863	1 287, 017 429, 330 46, 105	11, 145, 43 689, 999 83, 50	
Mexico Newfoundland and Labrador Philippine Islands	4, 021 26, 118	7, 206 63, 698	4, 978 63, 869	9, 669 159, 017	2,708	6, 97	
Spain Sweden	12, 331 236, 101	55, 793 968, 925	10, 864 8, 167	22, 254 50, 755	10	7	
United Kingdom Other countries	440 14	14, 290 287	612	19, 193	602	27, 679	
	2, 781, 222	6, 210, 971	2, 625, 261	5, 347, 277	819, 084	2, 142, 569	

<sup>1</sup> Includes pyrite cinder.

Exports of iron ore from the United States totaled 2,817,235 short tons valued at \$8,114,586 (\$2.88 a ton) in 1942 compared with 2,136,525 tons valued at \$6,212,308 (\$2.91 a ton) in 1941.

#### MINING IN CUBA

Because of war-shipping limitations, shipments from Cuban mines in 1942 were only 9 percent of those made in 1941. The 1942 total of 20,208 short tons included 4,575 tons from the Daiquiri-Juragua mines, averaging (dried) 56.12 percent iron; 2,371 tons from the Estancia mine, averaging (dried) 27.35 percent iron; and 13,262 tons of nodulized brown ore from the Mayari mine, averaging (dried) 56.83 percent iron. The Mayari mine was idle during October, and the Estancia was active only the first 4 months of the year.

Stocks of usable ore totaled 228,071 short tons at the end of the year compared with 101,842 tons at the end of 1941.

Iron ore shipped from mines in the Province of Oriente, Cuba, 1884-1942, in short tons

Year	Juragua, Daiquiri, and Estancia (hematite and magne- tite)	Sigua (hematite)	Mayari (brown ore)	Guamá (hematite)	El Cuero (hematite)	Total
1884–1940	25, 019, 868 176, 628 6, 946 25, 203, 442	22, 891	4, 406, 312 47, 764 13, 262 4, 467, 338	46, 190	1, 011, 475	30, 506, 736 224, 392 20, 208 30, 751, 336

#### REVIEW OF LAKE SUPERIOR DISTRICT

Production and shipments.—The largest movement of iron ore in the history of Great Lakes shipping signalized 1942. A total of 102,596,379 tons of iron and manganese-bearing ores was moved from United States ports during the year compared with the previous record shipments of 89,213,359 tons in 1941 and 72,502,302 tons in 1916. For the first time in the history of Lake Superior commerce, iron ore was shipped in March. On March 25, 1942, the first uplake boat arrived at Marquette, Mich., and on March 26 another boat reached Duluth. A total of 887,665 tons of ore was shipped in March and 8,723,884 tons in April. Lake shipments reached a monthly record in July, when they totaled 14,933,801 tons. The lakes remained open long enough to permit the movement of 712,128 tons in December. Allrail shipments from the Lake Superior district in 1942 totaled 1,563,490 tons.

A new all-time output of ore from the iron ranges in the Lake Superior district was made in 1942. Production of crude iron ore in the Lake Superior district amounted to 115,773,591 tons, a 16-percent increase over the 99,921,135 tons mined in 1941. Usable iron ore produced in the Lake Superior district, comprising direct shipping ore, concentrates, and sinter, totaled 101,925,624 tons, an increase of 15 percent over 1941. The Lake Superior district supplied 82 percent of the United States crude ore and 86 percent of the usable ore in 1942.

Of the six ranges contributing to the district total, the Mesabi was the largest producer, supplying 77 percent of the Lake Superior total and 67 percent of the United States total of usable ore in 1942.

Usable iron ore produced in the Lake Superior district, 1854-1942, by ranges, in short tons

Year	Marquette	Menominee	Gogebic	Vermilion	Mesabi	Cuyuna	Total
1854-1880	15, 977, 658	961, 866					16, 939, 524
1881-1890		13, 347, 506	9, 696, 747	3, 651, 676			47, 525, 702
1891-1900	30, 541, 890	24, 236, 657	26, 164, 368	13, 548, 694	36, 156, 817		130, 648, 426
1 <b>9</b> 01–1910		47, 011, 764	38, 656, 687	17, 192, 651	218, 013, 490		363, 130, 112
1911-1915		24, 485, 948	23, 930, 840	8, 102, 513	159, 847, 759	3, 574, 622	240, 554, 856
1916	5, 368, 145	7, 447, 527	8, 631, 953	1, 908, 973	46, 284, 382	1, 742, 318	71, 383, 298
1917	5, 194, 979	7, 130, 461	8, 826, 980	1, 659, 057	46, 062, 602	2, 225, 001	71, 099, 080
1918	4, 420, 140	6, 766, 633	8, 778, 150	1, 335, 798	43, 742, 694	1, 909, 953	66, 953, 368
1 <b>9</b> 19	4, 657, 801	5, 447, 644	8, 253, 273	1, 178, 010	37, 254, 508	1, 888, 182	58, 679, 418
1920	4, 992, 522	6, 329, 727	9, 293, 991	1, 179, <b>9</b> 40	41, 038, 906	1, 968, 708	64, 803, 794
1921		2, 405, 277	3, 511, 734	1,099,365	18, 345, 813	503, 506	28, 334, 303
1922		3, 685, 518	5, 500, 084	1, 241, 816	29, 909, 153	1, 070, 266	44, 481, 938
1923		5, 503, 166	6, 846, 181	1, 253, 407	46, 826, 100	1, 590, 585	66, 399, 657
1924		4, 234, 344	6, 249, 469	1, 278, 693	33, 397, 241	1, 054, 402	50, 222, 726
1925	4, 271, 329	5, 610, 105	7, 143, 035	1, 491, 563	39, 033, 242	754, 188	58, 303, 462
1926		6, 099, 165	7, 783, 910	1, 757, 227	42, 557, 533	1, 271, 047	64, 000, 616
1927	4, 497, 618	6, 113, 164	7, 397, 409	1, 767, 155	36, 809, 958	1, 139, 361	57, 724, 665
1928		5, 438, 423	7, 103, 143	1, 823, 684	39, 039, 093	1, 208, 909	58, 819, 236
1 <b>9</b> 29	5, 091, 340	6,079,885	7, 940, 354	2, 109, 573	47, 455, 735	1, 686, 853	70, 363, 740
1930	4, 950, 194	4, 962, 806	6, 735, 692	2, 236, 098	35, 055, 888	1, 367, 892	55, 308, 570
1 <b>9</b> 31	2, 969, 116	2, 333, 136	4, 142, 016	1, 322, 971	17, 470, 619	744,813	28, 982, 671
1 <b>9</b> 32	840, 775	906, 529	1, 596, 048	405, <b>5</b> 93	4, 766, 154	601, 058	9, 116, 157
1933	1, 110, 596	628, 889	1, 242, 443	338,000	12, 730, 831	313, 597	16, 364, 356
1 <b>9</b> 34	2, 610, 469	961, 023	2, 746, 300	876, <b>5</b> 03	16, 145, 077	215, 075	23, 554, 447
1935	3, 209, 127	818, 111	2, 685, 753	948, 211	20, 522, 538	228, 828	28, 412, 568
1936	4, 954, 230	1,839,654	4, 570, 560	1, 175, 689	33, 830, 023	424, 440	46, 794, 596
1937	6, 307, 206	2, 568, 204	5, 953, 558	1, 696, 007	51, 823, 370	707, 646	69, 055, 991
1 <b>9</b> 38	3,009,119	1, 437, 591	3, 235, 490	1,044,406	14, 847, 398	291, 417	23, 865, 421
1939	4, 374, 938	2, 152, 308	4, 820, 489	1, 568, 382	33, 064, 894	700, 149	46, 681, 160
1940	5, 918, 297	3,000,888	6, 462, 800	1, 715, 799	50, 941, 464	807, 965	68, 847, 213
1941	6, 978, 285	4, 281, 145	6, 780, 885	2, 075, 394	66, 850, 613	1, 354, 957	88, 321, 279
1942	7, 083, 224	5, 385, 930	6, 712, 804	2, 167, <b>3</b> 40	78, 722, 184	1, 854, 142	101, 925, 624
Total	245 697 687	219, 610, 994	259 393 146	81, 150, 188	1, 398, 546, 079	33, 199, 880	2, 237, 597, 974

[Exclusive after 1905 of ore containing 5 percent or more manganese]

Shipments from the Michipicoten range in Ontario, Canada, were made to the lower Lake ports for consumption by the Canadian iron and steel industry. This output is not included in Bureau of Mines Shipments of sinter from the Helen mine of the Algoma statistics. Steel Corporation totaled 545,066 short tons in 1942 compared with 518.277 tons in 1941. There was much interest during the year concerning the iron-ore deposits at Steep Rock Lake, in the Lake Superior region, Ontario, Canada. Diamond and churn drilling during 1942 developed indicated reserves of 14,377,000 tons, in addition to 1,525,000 tons of measured Bessemer-grade hematite having an analysis of 62.55 percent iron and 0.17 phosphorus. To exploit the deposit, it will be necessary to divert waters flowing into the lake and build dams so that water covering the deposit can be pumped out. The upper part of the deposit will be mined by an open-cut; however, most of the ore will be mined by underground methods.

Analyses.—The accompanying table was compiled by the Lake

Superior Iron Ore Association.

Average analyses of total tonnages (bill-of-lading weights) of all grades of iron ore from all ranges of Lake Superior district, 1938-42

Year	Short tons	Iron (nat- ural)	Phos- phorus	Silica	Manganese	Moisture
1938	21, 675, 917 50, 381, 804 70, 905, 423 89, 534, 189 103, 118, 290	Percent 51.90 51.75 52.09 51.83 51.65	Percent 0.089 .085 .085 .085 .085	Percent 8. 25 8. 27 8. 00 8. 18 8. 21	Percent 0.81 .76 .77 .78 .79	Percent 10. 13 10. 73 10. 93 11. 01 10. 98

Stocks at Lake Erie ports.—On December 1, 1942, just before navigation stopped, the Lake Superior Iron Ore Association reported 8,009,612 short tons of iron ore at Lake Erie ports, compared with 5,924,931 tons on the same date in 1941. At the opening of the 1943 shipping season in May 1943, 3,152,789 short tons of ore were in stock at these ports, compared with 2,832,676 tons on May 1, 1942. Withdrawals from stocks during this 5-month period in 1942–43 were 57

percent greater than in 1941-42.

Prices of Lake Superior ore.—The prices established April 17, 1940, for the four standard grades of Lake Superior ore remained unchanged. Since that date the price of the various grades quoted at Lake Erie ports for a short-ton unit were as follows: Old-Range Bessemer, 8.235 cents; Mesabi Bessemer, 7.975 cents; Old-Range Nonbessemer, 7.975 cents; and Mesabi Nonbessemer, 7.715 cents; respectively, \$4.24, \$4.11, \$4.11, and \$3.97 a short ton. The base of the four standard grades for 1925–42 is an iron content of 51.5 percent natural. For the bessemer grades, the allowable phosphorus content is 0.045 percent (dry), and for the nonbessemer grades the phosphorus content ranges from 0.045 to 0.18 percent. Ores containing more than 0.18 percent phosphorus are classed as high-phosphorus ores, whereas those containing 18 percent or more silica are classed as siliceous ores.

Reserves.—During 1942 there was considerable discussion concerning the possible depletion of high-grade iron-ore reserves on the Mesabi range. War requirements will amount to 100,000,000 tons of iron ore to be provided annually by the Lake Superior district. As produc-

tion from underground mines and concentrating plants is limited, most of the output must be supplied by open-pit direct shipping ore.

Davis 6 has pointed out that where a deposit of iron ore is flat-lying and is not covered by too much overburden, it is ordinarily mined by open-pit methods; and simply by putting additional shovels into operation and providing the necessary additional transportation, production from open-pit mines can often be doubled or tripled, whereas increasing the production from underground mines is not nearly so simple. The rate of production from an underground mine depends largely on the number of mining faces that can be worked simultaneously, and the maximum rate at which the ore is to be mined is established before an underground mine is opened. Consequently, it is not ordinarily possible to increase the rate of production radically.




FIGURE 3.—Rates of production, discoveries, and depletion of reserves, Mesabi range, 1910-42.

Actual reserves of the Lake Superior district are not given in the reports of the tax commissions of the various States. Although these commissions have access to all records of the mining companies and compile figures on reserves for the different ranges from them, the figures represent taxable reserves, and the actual tonnages that will eventually be produced from the Lake Superior district will exceed the tax commission estimates. Past records indicate that this excess may be considerable. Figure 3 compares cumulative production and discoveries with reserves on the Mesabi range from 1910 to 1942. During this period, 1.15 billion tons of iron ore were mined. this depletion was offset in large part by additions to reserves totaling 0.80 billion tons, so that known reserves decreased only 0.35 billion At current rates of production, it is evident that the known reserves will be exhausted in a relatively short period. Although addi-

<sup>6</sup> Work cited in footnote 3.

tions to reserves during the past 3 decades have offset depletion to a large extent, continuation of this trend into the future will depend on the ability of producers to find additional ore and the extent to which present low- and off-grade deposits become commercial in the future.

Unmined iron-ore reserves in Minnesota, May 1, 1938-42, in short tons

Range	1938	1939	1940	1941	1942
Mesabi Vermilion Cuyuna	1, 288, 915, 900 15, 986, 908 67, 973, 468	1, 268, 414, 950 15, 267, 262 69, 331, 231	1, 257, 304, 301 14, 793, 743 72, 829, 434	1, 228, 640, 029 15, 701, 206 72, 813, 737	1, 198, 122, 968 16, 691, 755 72, 141, 173
	1, 372, 876, 276	1, 353, 013, 443	1, 344, 927, 478	1, 317, 154, 972	1, 286, 955, 896

# Iron-ore reserves in Michigan, January 1, 1939-43, in short tons

Range	1939	1940	1941	1942	1943
Gogebic	45, 310, 722 58, 386, 031 64, 028, 731	41, 620, 208 55, 522, 649 63, 753, 461	35, 396, 179 54, 174, 528 62, 554, 000	33, 682, 351 54, 102, 855 62, 865, 694	36, 850, 185 57, 110, 705 62, 231, 371
	167, 725, 484	160, 896, 318	152, 124, 707	150, 650, 900	156, 192, 261

# MINING BY STATES

Alabama.—Production of crude iron ore in Alabama in 1942 was 35 percent greater than in 1941. Mining activity in this State trended away from small operations; this is indicated by statistics which show that despite the increase in output there were only 47 active mines in 1942, compared with 76 in 1941. The small operators were unable to obtain much necessary equipment and labor. addition, some of the operators entered the armed forces, and others went to work in war plants. Hematite represented 56 percent of the total crude-ore production in Alabama in 1942, and about 82 percent of the hematite produced was shipped direct to furnaces, 14 percent was sintered, and 4 percent was concentrated. In 1942, 55 percent of the total crude-ore production came from underground mines, most of which are in Jefferson County. The most important producing mines in this county were the Muscoda, Wenonah, and Ishkooda, which comprise the Red Mountain group, operated by the Tennessee Coal, Iron & Railroad Co. Other important underground mines in Jefferson County were the Spaulding and Raimund mines of the Republic Steel Corporation, the Woodward No. 3 mine operated by the Woodward Iron Co., and the Ruffner and Sloss Nos. 1 and 2 mines of the Sloss-Sheffield Steel & Iron Co. The usable hematite produced in Alabama in 1942 averaged (natural) 35.03 percent iron, 0.16 percent manganese, 0.32 percent phosphorus, 15.21 percent silica, and 14.97 percent lime.

Crude brown-ore (limonite) production in Alabama in 1942 amounted to 6,930,768 tons. This ore is mined by open-cut methods from a number of widely scattered deposits. All of this ore is concentrated before being consumed in blast furnaces. Log washers are commonly used for this purpose. Brown-ore concentrates produced in 1942 totaled 1,367,246 short tons, an increase of 12 percent over 1941. In 1942 the principal brown-ore mines were the Russellville Nos. 5,

11, and 12, operated by the Sloss-Sheffield Steel & Iron Co., the Giles mine of the Central Iron Ore Co., and the Martaban and Greeley mines of the Tennessee Coal, Iron & Railroad Co. Other important producers were the La Grange, Ironaton, Parish, Doc Ray, Waco, and Reno mines. Most of the brown-ore production came from Franklin, Tuscaloosa, Blount, Colbert, Butler, Talladega, and Cherokee Counties. Usable brown-ore production in 1942 averaged 46.0 percent iron, 0.63 percent manganese, 0.53 percent phosphorus, and 10.4 percent silica.

Arizona.—A small quantity of hematite was produced in Yuma County during the year. An open-cut mine is operated by E. E. Carlisle and produces ore for acid electric furnaces at Alhambra, Calif.

California.—The demands of the shipbuilding industry on the West coast caused 1942 usable iron-ore production in California to increase 78 percent over 1941. The Vulcan mine, an open-cut in San Bernardino County operated by the Kaiser Steel Co., made initial shipments of hematite to Fontana in December. Hematite from the Cave Canyon mine, the largest producer in the State, was shipped for consumption in cement manufacture. Magnetite from the Heroult mine in Shasta County was used largely for making concrete ballast blocks for shipping vessels. Shipments of usable ore in 1942 averaged 56.3 percent iron.

Georgia.—Virtually all of the output from Georgia is brown ore produced from open pits. Production of crude ore in 1942 totaled 1,506,265 tons, resulting in 334,342 tons of usable ore. The concentrating ratio of crude ore to usable ore was about 4.5:1. The outstanding producers in 1942 were the Porter, Woodward, Clemmons Hill, and Blanchard Reed mines and properties operated by the Mitchell & Hodge Co. and the Chulafinee Ore Co. Most of the ore

came from Polk and Bartow Counties and relatively small amounts from Cherokee, Floyd, and Walker Counties. Shipments of usable ore from Georgia during the year averaged 47.3 percent iron and 0.59 percent manganese.

Michigan.—Output in Michigan comes from three ranges—Marquette, Menominee, and Gogebic. During the year the output from the Marquette range increased slightly, and the Menominee range showed a substantial gain, but production from the Gogebic range decreased slightly from 1941. Production in Michigan during 1942 totaled 17,499,060 short tons of usable iron ore, an increase of 6 percent over 1941. Underground mines supplied 94 percent of the total output in 1942. The iron content of ore produced in Michigan during

the year averaged 51.68 percent, the same as in 1941.

The Negaunee and Maas mines, situated on the Marquette range and operated by the Cleveland-Cliffs Iron Co., were the leading producers in 1942, with 1,238,497 and 988,287 short tons, respectively. The Penn Group, Cliffs Shaft, Athens, Geneva-West Davis and Hiawatha Nos. 1 and 2 were also important producers. All of these underground mines produced hematite. The Plymouth mine on the Gogebic range was the largest open-pit producer in Michigan during the year.

Considerable expansion of the Michigan iron-ore industry was accomplished during 1942. The Sherwood mine of the Inland Steel Co., near Iron River, Mich., on the Menominee range, came into production in 1942. The Wauseca mine of the M. A. Hanna Co.,

also on the Menominee range, became an active producer in 1942, as did the Princeton mine of the Cleveland-Cliffs Iron Co. The Mather mine, at Ishpeming, Mich., owned jointly by the Cleveland-Cliffs Iron Co. and the Bethlehm Steel Co., was developed by the Negaunee

Mine Co., although no output was reported in 1942.

A report of the iron-ore mines of Michigan for 1942, published by the Geological Survey Division of the Michigan Department of Conservation, shows that the average number of men employed was 8,242 (7,553 in 1941), the average number of days worked 273 (248 in 1941), the average daily wage \$7.60 (same as 1941), the average yearly earnings \$2,073.53 (\$1,885.79 in 1941), and the average tons of ore mined per man per day 6.75 (7.15 in 1941).

The data in the following table on average per-ton costs of mining ore at underground mines and at siliceous open pits have been abstracted from statistics published in much greater detail by the

Geological Survey Division of Michigan.

Average costs, per short ton, of mining iron ore at underground mines and at siliceous open pits in Michigan in 1942

		Und	erground		
Îtem	Gogebic	Mar- quette	Menom- inee	Total	Siliceous open pits
Cost of mining:					
Labor Supplies Suppli	\$1. 0227 . 4950 . 2183 . 1954 . 1687 1. 6387 . 0600	\$1. 1325 . 4875 . 0518 . 1470 . 1820 1. 3604 . 0860	\$0. 9675 . 5192 . 1151 . 0899 . 1413 1. 4502 . 0696	\$1. 0503 . 4999 . 1175 . 1409 . 1653 1. 4773 . 0742	\$0. 2254 . 2154 . 0487 . 0417 . 0908 1. 3639 . 0714
Total ore cost Lake Erie value per ton	3. 7988 4. 2196	3. 4472 4. 1989	3. 3528 3. 9442	3. 5254 4. 1214	2. 0573 2. 0771
Gross ore profit 1	. 4208	. 7517	. 5914	. 5960	. 0198
Other costs: Royalty Interest on borrowed money Federal income and excess profits	. 3113 . 0002 . 1071	. 2023 . 0293 . 1975	. 2166 . 0033 . 0843	. 2369 . 0132 . 1356	. 0755 . 0056 . 0246

<sup>&</sup>lt;sup>1</sup> This figure does not represent true profit, as much ore is sold below the Lake Erie price.

Minnesota.—A record total of 96,693,590 tons of crude iron ore was produced in Minnesota in 1942, an increase of about 18 percent over 1941; open-pit mines supplied about 94 percent of the total. Sixty-six percent of the crude ore shipped was for direct use in blast and steel furnaces, and the remainder was shipped to concentrating plants. Concentrates represented about 23 percent of usable ore shipped from mines in Minnesota, sinter accounted for less than 1 percent, and the remainder was direct shipping ore.

Three ranges (Cuyuna, Mesabi, and Vermilion) contribute to Minnesota's production. Production in 1942 from the Mesabi comprised about 96 percent of Minnesota's crude ore and 95 percent of usable ore output. In Minnesota 34 of the 101 active mines produced more than 700,000 tons of crude ore each during the year. The iron content (natural) of the usable ore produced in 1942 averaged 52.11 percent

iron compared with 52.43 percent in 1941.

<sup>&</sup>lt;sup>7</sup> Pardee, F. G., General Statistics Covering Costs and Production of Michigan Iron Mines: Michigan Dept. of Conservation, Geol. Survey Div., Lansing, 1943, 9 pp.

During the year, the Evergreen Mines Co. completed a concentrating plant at the Maroco mine, which will serve the Maroco and

several other mines on the Cuyuna range.

Missouri.—Output of usable iron ore in 1942 totaled 59,180 tons, over three times the amount produced in 1941. The various properties of the Missouri-Cliffs Mining Co. supplied 83 percent of the State output. However, the Christy and Pioneer mines operated by the Missouri Mining Co. were important producers. Both hematite and brown ore were produced in Missouri; 93 percent came from open-pit mines. Usable ore shipped from mines in Missouri averaged 49.74 percent iron in 1942.

New Jersey.—Crude iron-ore production in 1942 totaled 1,494,853 tons, an increase of about 5 percent over 1941. The usable ore produced totaled 676,537 tons, a 7-percent decrease from the 1941 figure. To produce 1 ton of concentrates, 2.1 tons of crude ore were used in 1941 compared with 2.4 tons in 1942. This change in ratio may be caused by the variation of iron content in the ore; the proportion of ore to country rock mined; and the efficiency of the concentrator.

The Scrub Oaks mine, operated by the Alan Wood Steel Co., continued to be the outstanding producer in New Jersey. Other mines active in 1942 were the Mount Hope, Richard, and Washington. The magnetite ore is produced from underground mines in Morris and Warren Counties. The magnetite concentrates produced average

(natural) 62.89 percent iron.

New Mexico.—Most of the iron ore produced in New Mexico in 1942 came from the El Paso iron claim in Grant County, operated by the St. Louis Smelting & Refining Co. Seven new mines in Lincoln and Socorro Counties supplied the remainder of the State output. The hematite and the magnetite that came from both underground mines and open pits were shipped direct to furnaces in Colorado. A total of 107,306 tons of ore was mined, averaging 54.85 percent

iron. No production was reported in 1941.

New York.—The mining industry in the Adirondack district was greatly expanded during 1942. This expansion was not shown by production figures, because the activity was confined mostly to mine development and the construction of surface plants, although two new mines came into production on a small scale during the year. Late in the summer of 1942, the National Lead Co. made the initial shipments of magnetite and ilmenite concentrates from the MacIntyre mine 8 on Lake Sanford near Tahawus, Essex County. The Clifton mine near De Grasse, St. Lawrence County, was brought into production by the Clifton Ore Co. during the year. At the Clifton mine, most of the magnetite ore will be mined by underground methods, although open-pit methods of mining were used in 1942.

Surface structures, including magnetic separators and sintering plants, were under construction at the Benson mine in St. Lawrence County and the Fisher Hill mine near Mineville, Essex County. The magnetite deposit at the Benson mine will be exploited by the Jones & Laughlin Ore Co., using open-pit methods. At the Fisher Hill mine considerable underground development was done by the Republic Steel Corporation, although no production was reported during the year. A new inclined shaft, constructed at Mineville to serv-

<sup>8</sup> Matthews, Allan F., Minor Metals: Minerals Yearbook, 1941,

ice the Harmony-Old Bed-New Bed group should increase the output and efficiency of the mines by eliminating much rehandling of the crude ore. The Chateaugay mine at Lyon Mountain and the Mineville properties continue to be the outstanding iron-ore producers in the State. Shipments from New York State averaged (natural) 65.95 percent iron, 0.07 percent manganese, and 0.09 percent phos-

phorus.

Pennsylvania.—In 1942 the Cornwall mine, operated by the Bethlehem Steel Co., continued to supply virtually all of the ore produced in Pennsylvania. The magnetite ore body at Cornwall is mined by both underground and open-pit methods. The crude ore is hauled about 6 miles by rail to Lebanon, where all of the ore is concentrated and part of the concentrates sintered. In previous years the crude ore shipped from Cornwall was included with usable ore statistics. However, in 1942 a break-down is made between crude ore and usable ore, the concentrates and sinter shipped from Lebanon being included, for the first time, in usable ore statistics. It is believed that this new method of handling Cornwall figures will make the statistics more comparable with those of other magnetite mines, although the figures for this mine in 1942 will not be comparable with those for previous years.

The Hazard and Little Gap mines operated by the Prince Manufacturing Co. produced a small quantity of carbonate ore during the

year.

Tennessee.—The treatment of copper-iron ores by the Tennessee Copper Co. at Ducktown results in the production of a considerable amount of pyrite ash. This residue is sintered and shipped for consumption in blast and open-hearth furnaces. The tonnage of this byproduct material produced is included in usable ore statistics in 1942. Shipments of sinter during the year averaged 67.2 percent iron, 0.15 percent manganese, 0.007 percent phosphorus, and 2.2 percent silica.

Texas.—The Linden mine in Cass County was the only producer in the State in 1942; the brown ore shipped after concentrating averaged

52.5 percent iron.

Utah.—In 1942 the Iron Mountain mine operated by the Columbia Steel Co. continued to supply most of the iron ore output from Utah. The ore, principally semialtered magnetite, was mined by open-cut methods. Most of the ore was shipped to the blast furnace at Provo and contained (natural) 53.49 percent iron. The Great Western mine operated by Helene Beatty was the only other producer in the State.

Virginia.—The American Pigment Corporation mine in Pulaski County supplied virtually all of the output in 1942. The brown ore is mined from an open-cut and is consumed by the paint industry.

Washington.—Most of the ore produced in Washington during the year was from the Neutral mine in Okanogan County. This magnetite ore was used for ballast in war vessels. Some hematite was produced from the Napoleon mine in Stevens County and the Keystone mine in Pend Oreille County.

Wisconsin.—Production of crude hematite from underground mines in 1942 increased 5 percent over 1941. Ore from the Montreal Mining Co., averaged (natural) 52.48 percent iron, 1.26 percent manganese, 0.51 percent phosphorus, and 6.63 percent silica. The Cary mine, operated by the Odanah Iron Co., produced ore containing

(natural) 53.13 percent iron, 0.82 percent manganese, 0.05 percent phosphorus, and 6.07 percent silica. During the year a small quantity of ore was shipped from the Matilda-mine stock pile.

Wyoming.—The Sunrise mine in Platte County supplied all of the Wyoming output in 1942. Production came from both open-pit and underground operations by the Colorado Fuel & Iron Corporation. Shipments of hematite averaged (natural) 49.89 percent iron, 0.09 percent manganese, 0.06 percent phosphorus, and 12.95 percent silica.

Crude iron ore mined in the United States in 1942, by States and counties [Exclusive of ore containing 5 percent or more manganese]

State and county	Active mines	Short tons	State and county	Active mines	Short tons
Alabama:			Missouri:		
Alabama: Bibb	11	140	St. Francois	} 2	450
Etowah	1	148	Washington	2	458
Blount	1	168,000	Washington Crawford, Miller, Frank-		
Butler	12	} 415, 150	lin, Phelps, Howell, Ore- gon, and various	1	
Crenshaw	1		gon, and various	1 2	67,650
Calhoun	12	293, 328		<u> </u>	
Cherokee	1 5	309, 939		. 14	68, 108
Chilton	2	8,064			
Clay	11	33, 600	New Jersey:		
Colbert	1	534, 012	Morris	3	1, 494, 853
Franklin	18	2, 226, 185	Warren	1	J -, 10-, 000
Jefferson	12	8, 678, 263			1 101 070
Marshall	11	12, 320		4	1, 494, 853
Pike	11	13, 664	37		
Talladega	14	426, 681	New Mexico:		
Tuscaloosa	. 4	2, 489, 759	Grant	1 1 6	107.000
the second secon		15 600 110	Lincoln		107, 306
	1 47	15, 609, 113	Socorro	1	IJ
Arizona: Yuma	1	386		18	107, 306
Yuma	1	500	New York:		107,300
0-1/0			Clinton	1	,
California:	1	319	Essex	2	H
Inyo San Bernardino	2	90, 159	Oneida	í	
Santa Cruz	\ 1	196	St. Lawrence	1 1	5, 444, 703
	` 1	15,846	Pennsylvania:	1	]]
Shasta		10,040	Lebanon	1	! !
	5	106, 520	Carbon	i	1, 146
		100,020	Carbon		1,110
Georgia:				7	5, 445, 849
Bartow	17	501, 101			0, 110, 010
Cherokee	11	8,064	Texas:	1	}
Floyd	î	112	Cass	1	h
Polk	1 10	991,860	Virginia:	_	
Walker	1	5, 128	Botetourt	1	51,757
11 44410			Pulaski	1	)
	. 1 20	1, 506, 265		<u> </u>	<u> </u>
				3	51,757
Michigan:			Utah:	_	
Dickinson	3	996, 846	Iron	2	359, 558
Gogebic	8	5, 029, 907	l		
Iron	18	4, 389, 084	Washington:		
Marquette	15	7, 083, 223	Wasnington: Okanogan Pend Oreille	1	11,536
			Pend Oreille	1	302
	44	17, 499, 060	Stevens	1	1,446
					10.004
Minnesota:			l	3	13, 284
Crow Wing	10	2, 146, 514 101, 956	Wisconsin: Iron		4 000 007
Fillmore	1	101,956	iron	2	1, 682, 897
Itasca	33	33, 681, 280	Wyoming: Platte	l -	1 051 050
St. Louis	57	60, 763, 840	Platte	1	1,071,870
	101	96, 693, 590	II.	1 252	141, 710, 416

In addition, there is an undetermined number of small pits. The output of these pits is included in the tonnage given.

# EMPLOYMENT AT IRON MINES

Although complete information on employment at iron-ore mines in 1942 is not yet available, incomplete figures indicate that about 31,000 men worked 64,000,000 man-hours to produce 117,469,164 short tons of usable ore from domestic mines—an average of about 1.8 tons per man-hour and an all-time record. The man-hours worked in 1942 increased 6 percent over 1941, whereas the output of usable ore from domestic mines increased 13 percent; consequently, the output per man-hour increased 7 percent. The gain in output per man-hour was due mainly to open-pit mines, which represented 68 percent of the increase in production in 1942 over 1941.




FIGURE 4.—Trends in number of men employed at iron-ore mines, output of merchantable (usable) ore, man-hours worked, and output per man-hour in the United States, 1923-41.




FIGURE 5.—Trends in output of merchantable (usable) iron ore per man-hour at open-pit mines in Minnesota compared with production of merchantable (usable) and lean ore and total man-hours worked, 1923-41.




FIGURE 6.—Trends in production, man-hours worked, output per man-hour, and number of men employed at iron-ore mines in Jefferson County, Ala., 1923-41.

			Employme	ent					Pro	duction					
			Time	mployed	l			Usable ore			Avera	ge per m	an (shor	tons)	
District and State	Average number	Aver-		Ma	n-hours	Crude ore		Iron con	tained	Crud			Usab	le ore	-
	of men employed	age num-	Total man-	Aver-		(partly estimated), short tons	Short tons			(partl) mat	y esti- ed)	Per	Per	Iron co	ntained
	employed	ber of days	shifts	age per shift	Total	SHOPE CORS		Short tons	Percent natural	Per shift	Per	shift	hour	Per shift	Per hour
Lake Superior: Michigan Minnesota Wisconsin	7, 477 10, 303 785	276 247 261	2, 061, 853 2, 546, 851 205, 129	8. 0 8. 0 8. 0	16, 494, 306 20, 339, 871 1, 641, 032	16, 431, 735 81, 880, 819 1, 608, 581	16, 431, 735 70, 281, 016 1, 608, 581	8, 491, 851 36, 848, 463 857, 690	51. 68 52, 43 53, 32	7. 969 32. 150 7. 842	0, 996 4, 026 , 980	7. 967 27. 595 7. 842	0. 996 3. 455 . 980	4. 119 14. 468 4. 181	0. 515 1. 812 . 523
<b>a</b>	18, 565	259	4, 813, 833	8.0	38, 475, 209	99, 921, 135	88, 321, 332	46, 198, 004	52. 31	20.757	2. 597	18, 347	2, 296	9. 597	1, 201
Southeastern States: Alabama Georgia Mississippi Virginia	6, 159	262 157	1, 615, 508 41, 558	8. 2 9. 0	13, 208, 120 373, 678	11, 543, 516 1, 266, 602 } 428	8, 831, 033 291, 947 428	3, 280, 489 136, 944 224	37. 15 46. 91 45. 80 53. 60	7. 145 30. 488	. 874 3. 391	5, 466 7, 035	. 669 . 782	2, 031 3, 301	. 248
	6, 423	258	1, 657, 066	8. 2	13, 581, 798	12, 810, 546	9, 123, 408	3, 417, 657	37, 46	7, 732	. 943	5, 506	. 672	2. 062	. 252
Northeastern States: Connecticut New Jersey New York Pennsylvania	} 923 } 2, 106	266 339	245, 085 713, 385	8. 0 7. 4	1, 956, 610 5, 304, 048	99 1, 429, 556 4, 855, 258	99 727, 299 3, 710, 123	45 453, 452 1, 790, 812	45. 00 62, 35 66, 92 39, 64	} 5,833 } 6.806	.731	2. 968 5. 201	. 372	1. 850 2. 510	. 232
•	3, 029	316	958, 470	7.6	7, 260, 658	6, 284, 913	4, 437, 521	2, 244, 309	50, 58	6, 557	. 866	4, 630	. 611	2, 342	. 309
Western States: California. Missouri Nevada Oklahoma. Utah Washington. South Dakota Texas Wyoming.	190	173	32, 841 98, 606	8.0	262, 823	60, 293 20, 891 241 233 397, 607 11, 674 34, 242 1, 104, 154	59, 955 20, 891 241 233 397, 607 11, 674 21, 713 1, 104, 154	33, 124 10, 842 109 110 216, 579 7, 744 11, 244 567, 093	55, 25 51, 90 45, 00 47, 10 54, 47 66, 30 46, 00 52, 50 51, 36	) 15. 992 11. 198	1, 998	15. 600	1. 949	8. 518 5. 751	1. 064
• •	570	235	131, 447	8.0	1, 051, 671	1, 629, 335	1, 616, 468	846, 845	52, 39	12. 395	1. 549	12, 297	1. 537	6, 442	.805
	28, 587	264		8.0		120, 645, 929		52, 706, 815	50, 93	15, 957	1. 998	13, 689	1. 714	6. 971	.873

# WORLD PRODUCTION

The following table shows the production of iron ore by countries from 1938 to 1942, insofar as statistics are available. Although complete returns are not available, it is probable that world production established a new record in 1942 because of the large increase in United States production.

World production of iron ore, 1938-42, by countries, in metric tons 1 [Compiled by B. B. Waldbauer]

					A . *
Country 1	1938	1939	1940	1941	1942
North America:					
Canada	5, 281	117, 583	376, 120	468, 138	494, 521
Cuba	234, 061	117, 583 166, 739	160, 339	192, 851	132, 847
Mexico Newfoundland	118, 251	143, 873	110, 783	110, 134	102, 526
Newfoundland	1, 707, 180	1, 679, 625	1, 532, 990	981, 735	3 1, 200, 000
United States	28, 903, 861	52, 562, 024	74, 878, 718	93, 892, 753	107, 219, 002
Couth & movies.		1,,		,,	
Brazil	359, 115	396, 938	255, 548	420, 756	308, 921
Chile 4	1,608,399	1, 626, 490	1,749,840	1, 702, 692	408, 587
Europe:		7 - 7		_,,,,,,,,,	200,00
Belgium	180, 920	177, 370	(2) 30,000 862,000	(2)	(2)
Bulgaria	16, 771	20, 115	30,000	(2)	(2)
Czechoslovakia 4	693,000	766,000	862,000	978,000	1,040,00
Czechoslovakia ś France	33, 137, 000	(6)	(2)	(2)	(2)
Germany 7	10, 938, 650	(6)	(2) (2) (2) (2) (2) (2) (2) (2) (2) (2)	(2)	(2)
Austria	2, 600, 063	(6)	25	(2)	l ≥2\(\)
Greece	348, 613	307, 284	(2)	(2)	2
Hungary	369, 935	370,000	2	2	(2)
Italy		(6)	1 2	2	2
Luxemburg		(6)	2	2	2
Morwow	1, 425, 297	1, 340, 408	1 2	1 🔀	\$ 300,00
Norway Poland	872, 591	(6)	1 2	(2)	(2)
Portugal	2, 519	418	301	287	\ \sum_2\
Rumania	139, 185	131, 992	(2)	(2)	2
Spain	2, 544, 945	3, 594, 294	2, 629, 609		1, 670, 37
Ome dem	13, 928, 023	10 707 000		1, 640, 687	1,070,07
Sweden Switzerland	13, 928, 023	13, 787, 202	(2)		
Switzeriand	133, 998	8 171, 279	200,000		(2)
U. S. S. R. <sup>o</sup> United Kingdom: Great Britain <sup>10</sup>	26, 529, 700	(6)	27, 500, 000		
United Kingdom: Great Britain	12, 049, 531	(6)	18, 000, 000	2 11 700 000	(2)
Yugoslavia	606, 884	666, 816	(2)	8 11 523, 000	(2)
Burma	18,340	26, 680	(2)	(2)	(2)
Chosen	(6)	(6)			(2)
India, British	0 707 711	3, 166, 087	(2)	2	1 3
Indochina	2, 787, 711			2	
Japan	(8)	136,000	32,861	(2)	(2)
Malay States:	(9)	(6)	(2)	(*)	(*)
Federated	020	700	070	(2)	(2)
Unfederated	1,606,289	780 1, 991, 173	972 1, 872, 903	(2)	(2) (2)
Philippine Islands *	910, 952	1, 154, 738	1, 191, 641	12 852, 080	(2)
Timppine islands	910, 904	1, 104, 700	1, 191, 041		
Turkey U. S. S. R	71, 375	143, 277	130, 338	(2)	(2)
U. D. D. R.	(9)···	(9)	(9)	(*)	(4)
Africa:	0.105.005	20 770 000	<b>(0)</b>	/m	(0)
Algeria	3, 105, 037	3 2, 750, 000	(2) 6, 100	(2) (2)	(2)
Belgian Congo	2,650	(6)	6, 100	(2)	(2)
Morocco:			(0)		
French		(6)	(2)	(2) (2)	(2)
Spanish	1, 341, 658	8 1, 038, 006	8 389, 337	(2)	8 555, 00
Northern Rhodesia	208	138	(2) (2) (2)	(2)	(2)
Sierra Leone	875, 789	(6)	(2)	(2)	(2)
South-West Africa		19, 500 764, 731	(2)	(2)	(2)
Tunisia		764, 731	(2)	(2)	(2)
Union of South Africa	505, 314	490, 136	638, 757	13 680, 041	13 607, 76
Oceania:	1		1		1
Australia:		1	1	j	1
Queensland	5, 207	4,003	(2)	(2)	(2)
South Australia	2, 281, 404	2, 613, 036	2, 350, 484	(2) 2, 276, 345	(2)
Tasmania	[	(6)	(2)	(2)	(2)
New Caledonia	36, 279	83, 567	176, 600	(2)	(2)
New Zealand	1, 238	1,611	1, 208	1,569	(2)
					<u>`</u>
	162, 000, 000	200, 000, 000	3212, 000, 000	3 233, 000, 000	3245, 000, 00
	12, 555, 666	1, 555, 566	, 555, 566	1	
		,		,	

In addition to the countries listed, China, Egypt, Eritrea, Finland, French West Africa, Madagascar, and New South Wales report production of iron ore, but complete data are not available.

Data not available.

Estimated.

Estimated Production of Tofo Mines.

Slovakia only.

Estimate included in total.

Exports.

U. S. S. R. in Asia included with U. S. S. R. in Europe.

Exports.

Line Asia included with U. S. S. R. in Europe.

Line Asia included with U. S. S. R. in Europe.

Line Asia included with U. S. S. R. in Europe.

Line Asia included with U. S. S. R. in Europe.

# SPONGE IRON

Considerable publicity was given to sponge iron during 1942 in view of an impending shortage of iron and steel scrap. Sponge iron of a usable grade for steel making can be produced by several techniques, including rotary and stationary kilns and multiple-hearth roasters. The economics of the operation depends on the scrap situation. When scrap is flowing to steel furnaces at a desired rate, sponge iron, if in powdered form, with more than a few percent of silica, and if special means of preventing entrance of sulfur during its production have not been used, would not be an economical melting stock in basic steel furnaces. However, during an emergency, the supply of scrap might not be adequate for maximum steel production and, with costs of secondary importance, there is little doubt that sponge iron could be used as a substitute for scrap. Early in our present steel-expansion program it seemed that such a shortage of scrap would develop; consequently, much publicity and speculation were given to the possibility of producing sponge in large quantities. Extensive use of sponge iron in steel furnaces would decrease steel-making capacity somewhat but would offset to some extent losses that might result from scrap shortages.

Except for metal powders, virtually no commercial sponge iron was produced in 1942. However, considerable progress was made in the development and construction of plants during the year. In October the War Production Board approved construction of a \$450,000 sponge-iron plant at Youngstown, Ohio, as an experimental project to test the use of the material in electric furnaces. Likewise, funds totaling \$600,000 were made available to the Bureau of Mines for construction and operation of sponge-iron pilot plants. Results of this work have

not yet been made public.

#### PIG IRON

## PRODUCTION AND SHIPMENTS

Domestic production of pig iron, exclusive of ferro-alloys, increased 7 percent in 1942 over 1941 and established a new record. The output in 1942 comprised 58,973,389 short tons using coke and 104,204 using charcoal as fuel. Pennsylvania was the largest producer of pig iron in 1942, with 31 percent of the total; Ohio ranked second, with 22 percent. Of the pig iron manufactured in 1942, it is calculated that 513,699 tons valued at \$11,326,032 were made from 900,924 tons of foreign ores, including ore from Africa, Australia, Brazil, Canada, Chile, Cuba, India, Newfoundland, Spain, and Sweden, indicating an average yield of 57.02 percent from imported ore. Domestic ore (103,154,498 tons) and cinder, scale, and purchased scrap (7,741,210 tons) totaling 110,895,708 tons were reported as used in the manufacture of 58,563,894 tons of pig iron, indicating an average pig-iron yield of 52.81 percent from domestic materials. In addition, 1,564,912 tons of home scrap and 4,177,674 tons of flue dust were consumed in making pig iron in 1942.

Pig iron produced and shipped in the United States, 1941-42, by States

	Prod	luced	Shipped from furnaces					
State	1941 (short	1942 (short	1	941	1	942		
1,000 9 90 0 50 200 200 9 90 0 10 10 10 10 10 10 10 10 10 10 10 10	tons)	tons)	Short tons	Value	Short tons	Value		
AlabamaColorado	3, 696, 566	4, 081, 710	3, 712, 018	\$64, 037, 109	4, 083, 330	\$70, 638, 989		
Illinois Indiana	5, 354, 767 6, 374, 331	5, 850, 070 6, 430, 820	5, 461, 459 6, 393, 223	113, 558, 606 135, 655, 190	5, 871, 858 6, 446, 750	125, 662, 134 142, 920, 764		
Kentucky Maryland	328, 912 2, 353, 203	457, 124 2, 490, 571	329, 125 2, 372, 932	300	457, 124 <b>2,</b> 493, 946	100		
Massachusetts Michigan Minnesota	1, 350, 450 359, 263	1, 683, 414 373, 492	1, 360, 139 369, 549	21, 384, 383	1, 675, 143 373, 595	25, 718, 214		
New YorkOhio	3, 574, 901 12, 787, 243	4, 040, 756 13, 140, 362	3, 724, 989 12, 995, 298	66, 718, 244 268, 660, 861	4, 011, 238 13, 153, 014 18, 038, 237	78, 734, 591 284, 600, 670		
Pennsylvania Tennessee Utah	16, 856, 917 (1)	18, 064, 888 (1) (1)	16, 340, 965 (1) (1)	344, 298, 435 (1) (1)	(1)	388, 006, 956 (1) (1)		
Virginia West Virginia Undistributed	1, 019, 150 1, 029, 743	1, 408, 993 1, 055, 393	1, 032, 148 1, 131, 796	(1) (1) 97, 498, 488	1, 417, 225 1, 079, 141	(1) (1) 111, 107, 374		
	55, 085, 446	59, 077, 593		1, 111, 811, 316	59, 100, 601	1, 227, 389, 689		

Shipments of pig iron, exclusive of ferro-alloys, increased 7 percent in quantity and 10 percent in value in 1942 over 1941. given represent the approximate amounts received for the iron f. o. b. furnaces and do not include freight costs, selling commissions, and other items figured in some of the market prices for pig iron published by trade journals.

Pig iron shipped from blast furnaces in the United States, 1941-42, by grades

		1941		1942			
Grade	a.	Valu	е	Ch t t	Valu	e	
	Short tons	Total	Average	Short tons	Total	Average	
Charcoal Foundry Basic Bessemer	144, 076 3, 125, 413 40, 642, 051 7, 900, 369	\$3, 618, 686 61, 309, 626 801, 328, 939 170, 051, 203	\$25, 12 19, 62 19, 72 21, 52	104, 813 2, 656, 089 44, 317, 871 8, 892, 477	\$2, 860, 086 53, 221, 988 900, 681, 890 197, 565, 272	\$27. 29 20. 04 20. 32 22. 22	
Low-Phosphorus  Malleable  Forge  All other (not ferro-alloys)	508, 727 2, 643, 497 1, 212 258, 296	13, 881, 518 56, 677, 298 30, 094 4, 913, 952	27. 29 21. 44 24. 83 19. 02	520, 642 2, 455, 295 153, 414	13, 998, 587 55, 642, 522 3, 419, 344	26. 89 22. 60 22. 20	
An other (net lette ane ye)	55, 223, 641	1, 111, 811, 316	20. 13	59, 100, 601	1, 227, 389, 689	20. 77	

The number of furnaces in blast June 30 and December 31 and the total number of blast furnaces recorded for 1941 and 1942 were as follows:

<sup>&</sup>lt;sup>1</sup> Included under "Undistributed."

<sup>1</sup> Includes statistics for States entered as "(1)."

Blast furnaces (including ferro-alloy blast furnaces) in the United States, 1941-42 1

<b>CLL</b>	In blast			, 1941	In blast	December 31, 1942		
State	June 30, 1941	In	Out	Total	June 30, 1942	In	Out	Total
AlabamaCalifornia	17	19	1	20	20	21		21
Colorado	3 18	3 20	1 3	4 23	3 20	3 19	1 2	4 21
Indiana Kentucky	19 2	19 2		19 2	19 2	19 3	1	20 3
Maryland Massachusetts Michigan	0 1 7	1 8		1 8	1 8	1 7		1
Minnesota New York	2 15	2 15	1	2 16	2 16	2 16	î 1	1
Ohio Pennsylvania	47 70	46 70	2 7	48 77	46 71	. 48 73	1 3	49 70
Tennessee Utah Virginia	$\frac{2}{1}$	5 1		5. 1	5 1	1	1	
West Virginia	3	4		4	4	4		-
	214	223	15	238	226	230	12	242

<sup>&</sup>lt;sup>1</sup> American Iron and Steel Institute.

#### VALUE AT BLAST FURNACES

The average value of all grades of pig iron given in the accompanying table is based upon reports of producers to the Bureau of Mines. The figures represent the approximate values f. o. b. blast furnaces and do not include the values of ferro-alloys. The general average value for all grades of pig iron at the furnaces was \$20.77 a short ton in 1942, \$0.64 more than in 1941.

Average value per short ton of pig iron at blast furnaces in the United States, 1938-42, by States

State	1938	1939	1940	1941	1942
Alabama	\$13.10	\$14.42	\$14.30	\$17. 25	\$17.30
Indiana	18. 15	18. 02	18. 05	20. 79	21. 40
Indiana	18. 29	18. 03	18. 26	21. 22	22. 17
Michigan	15. 67	14. 79	13. 78	15. 72	15. 35
New York	18. 58	18. 29	16.89	17. 91	19. 63
Ohio	18. 17	18. 12	18.81	20. 67	21. 64
Pennsylvania Other States 1	19.30	18. 52	19. 40	21.07	21. 51
	15.21	14. 91	15. 20	18.62	19. 09
Average for United States	17. 51	17. 44	17.90	20. 13	20.77

<sup>&</sup>lt;sup>1</sup> Colorado, Iowa, Kentucky, Maryland, Massachusetts, Minnesota, Tennessee, Utah, Virginia, and West Virginia.

#### COMMERCIAL QUOTATIONS

The average monthly prices of Foundry, Basic, and Bessemer pig iron at Valley furnaces and of Foundry pig iron at Birmingham furnaces, according to published market quotations, are summarized in the table following.

Average monthly prices per short ton of chief grades of pig iron, 1941-42 1

Month	iron at	iron at Valley   iron		Foundry pig iron at Birming- ham furnaces		Bessemer pig iron at Valley furnaces		Basic pig iron at Valley furnaces	
	1941	1942	1941	1942	1941	1942	1941	1942	
January February March April May June July August September October	21. 43 21. 43 21. 43 21. 43 21. 43 21. 43	\$21. 43 21. 43 21. 43 21. 43 21. 43 21. 43 21. 43 21. 43 21. 43	\$17. 30 17. 30 17. 51 18. 20 18. 20 18. 20 18. 20 18. 20	\$18. 20 18. 20 18. 20 18. 20 18. 20 18. 20 18. 20 18. 20 18. 20	\$21.88 21.88 21.88 21.88 21.88 21.88 21.88 21.88 21.88	\$21. 88 21. 88 21. 88 21. 88 21. 88 21. 88 21. 88 21. 88 21. 88	\$20, 98 20, 98 20, 98 20, 98 20, 98 20, 98 20, 98 20, 98 20, 98 20, 98	\$20. 98 20. 98 20. 98 20. 98 20. 98 20. 98 20. 98 20. 98 20. 98	
November December	21. 43 21. 43	21. 43 21. 43	18. 20 18. 20	18. 20 18. 20	21.88 21.88	21.88 21.88	20.98 20.98	20. 98 20. 98	
Average	21. 43	21. 43	17. 99	18. 20	21.88	21.88	20.98	20.98	

<sup>&</sup>lt;sup>1</sup> Metal Statistics, 1943.

# FOREIGN TRADE

There were no imports for consumption of pig iron during 1942.

Pig iron imported for consumption in the United States, 1938-42, by countries, in short tons 1

Country	1938	1939	1940	1941
North America: CanadaSouth America: Brazil	2, 975	7, 685 174	3,826	308
Europe: Denmark		1		
Netherlands Norway Sweden	15, 944 952 230	7, 250		
United Kingdom Asia: India, British	13, 900	27, 821	7, 645	0.00
Oceania: Australia	34, 048	43, 223	11, 471	3, 367
Value	\$598, 461	\$663,091	\$189,379	\$61, 130

<sup>1</sup> None imported in 1942.

Pig iron exported from the United States, 1941-42, by countries, in short tons

Country	1941	1942	Country	1941	1942
North America:	5, 118	1,691	Europe—Continued.	841	
CanadaCuba	21	1,091	Asia:	041	
Panama	458	127	British Malaya	171	
Other North America	274	63	China	280	
South America:			Netherlands Indies	2,897	168
Argentina	291	336	Philippine Islands	807	
Bolivia	6	235	Other Asia	70	
Chile	2, 119	578	Africa:	101	000
Colombia	441 1,064		Belgian Congo Gold Coast	121 39	263
PeruUruguay	1,004		Union of South Africa	7,075	
Other South America	131		Other Africa	1,013	59
Europe:	101		Oceania: New Zealand	203	1, 118
Portugal	570		Occupies 11011 Economics		1,110
U. S. S. R.	. <b></b>	430	(	578,533	110, 647
United Kingdom	555, 339	105, 495	Value		\$3, 144, 701

いのかれている。 とうないないとないないかいないないとうしょうかん

#### CONSUMPTION

Consumption of pig iron rose 5 percent in 1942 over 1941. Pig iron, a product of the blast furnace, is a semiraw material and, except for the small quantity used in direct castings, moves to other-type furnaces for further refining or mixture with other required ingredi-In general, it goes to steel-making or iron-making furnaces. By far the larger part is taken to steel-making furnaces (open-hearth, bessemer, and electric) for refining and processing into steel. 88 percent of the pig iron was consumed in steel making. castings took 4 percent of the 1942 total, and the remaining 8 percent was consumed in iron-making furnaces, of which the cupola is the most important. The consumption of pig iron, by types of furnace, for 1939 to 1942 is shown in the following table. The quantities of pig iron used in these furnaces are supplemented by the addition of ferrous scrap. The proportion of pig iron to scrap used in steel furnaces increased in 1942 over 1941.

Consumption of pig iron in the United States, 1939-42, by type of furnace

Type of furnace or	1939		194	0	194	1	1942	
equipment	Short tons	Percent of total	Short tons	Percent of total	Short tons	Percent of total	Short tons	Percent of total
Open-hearth Bessemer Electric Cupola 1 Air Brackelsberg	26, 826, 172 3, 603, 199 30, 542 3, 349, 198 329, 317	76. 2 10. 2 .1 9. 5	36, 297, 250 3, 828, 978 46, 506 4, 106, 119 374, 187	78.6 8.3 .1 8.9	42, 481, 404 5, 993, 264 72, 758 5, 388, 747 604, 835	75. 6 10. 7 . 1 9. 6 1. 1	45, 538, 846 6, 131, 222 92, 878 24, 490, 532 555, 436	77. 1 10. 4 . 2 7. 6
Crucible Puddling Direct castings 1	92 27, 959 1, 066, 220	(3) .1 3.0	184 28, 293 1, 504, 311	(3) .1 3.2	207 54, 183 1, 590, 074	(3) .1 2.8	221 49, 835 2, 183, 913	(³) .1 3.7
	35, 232, 699	100.0	46, 185, 828	100.0	56, 185, 472	100.0	2 59,042,883	100.0

Some pig iron used in making direct castings included in cupola.
 Includes 19 tons used in making ferro-alloys.
 Less than 0.05 percent.

The consumption of pig iron in this country is widespread, and plants using pig iron are situated in all 48 States, the District of Columbia, and Alaska. As expected from the uses of pig iron, consumption is concentrated largely in the iron- and steel-making centers of the North Central, Middle Atlantic, and Southeastern States. These areas in 1942 used about 98 percent of the pig iron, Pennsylvania (the leading consumer) taking about 32 percent of the total and Ohio (the second-largest consumer) 20 percent.

# Consumption of pig iron in the United States, 1939-42, by States and districts

	1	939		1940		1941	1	942
State and district	Con- sum- ers	Short tons	Con- sum- ers	Short tons	Con- sum- ers	Short tons	Con- sum- ers	Short tons
Connecticut	59	82, 886	60	96, 574	62	143, 862	61	138, 93
Agine	15	6, 720	15	8, 392	14	11, 467	13	8, 76
Jow Hampshire	15	1,826	14	2,479	15	5, 816 242, 265 57, 082	16	20, 52
	97	115, 534	104	146,886	107 12	242, 200 57 000	101 12	244, 99 58, 11
hode Island	12 12	26, 257 6, 530	11 12	146, 886 37, 308 10, 358	14	16, 276	12	20, 6
ermont  Total New England	210	239, 753	216	301, 997	224	476, 768	215	491, 98
Delaware	7		ر ر		7	} 449, 486	7	} 532, 78
lew Jersey	79	281,000	81	362, 758	<b>80</b>	J	84	1
ew York	193	1,817,251	190	2, 403, 248	199	2, 765, 216	200	3, 015, 4
ennsylvania	365	10, 152, 661	348	14, 634, 036	391	17, 573, 102	392	18, 843, 8
Total Middle Atlantic	644	12, 250, 912	626	17, 400, 042	677	20, 787, 804	683	22, 392, 00
labama	57	2, 378, 774.	59	2, 809, 064	74	3, 142, 958	71	3, 408, 9
	2 24	2, 365, 534	$\begin{cases} 1\\ 24 \end{cases}$	2, 825, 324	23	2, 974, 834	23	3, 055, 5
entucky faryland	26	(2,000,001	25	2,020,021	26	1,5,5,5	28	,,
	23	880,062	23	1, 016, 445	28	1, 218, 175	28 27	1,624,0
	12		13	73,045	ſ 12	83, 895	ſ 15	81, 2
	40	61,655	1 40	U	43		1 44	
eorgia Lississippi forth Carolina outh Carolina	7	362	9	365	7	621	6	10 6
orth Carolina	32	13, 853	33	15, 901	40 12	18, 591	42 14	16, 0 4, 5
outh Carolina	13	2, 251	14	2, 355	52	5,090	51	h
ennesseeirginia	52 46	150, 564	44	162, 936	45	254, 840	47	} 165, 3
Total Southeastern	334	5, 853, 055	335	6, 905, 435	363	7, 699, 004	369	8, 356, 3
			f 6		<u>f</u> 6		[ 3	<del></del>
rkansas	6	2,003	8	2, 107	7	2,600	7	3,0
klahomaouisiana	. 8	2,000	8	2, -0.	7		6	
exas	24	2,572	23	2, 327	27	3, 107	28	4,4
Total Southwestern	44	4, 575	45	4, 434	47	5, 707	44	7,4
	179	2, 770, 693	183	3, 764, 275	208	4 915 372	212	5, 369, 9
llinois	124	3, 830, 053	126	5 522 177	131	6, 833, 091	127	6, 963, 0
ndianaowa	49	54, 834	52	5, 522, 177 63, 834 214, 340	52	4, 915, 372 6, 833, 091 104, 368	54	64,0
/innecota	53	54, 834 185, 976 37, 760	51	214, 340	53	266, 768 80, 065	57	308, 9
/issouri	53	37, 760	53	45, 486	51	80,065	53	81,6
Cansas	14	3, 513	J 13	3,742	[ 15	4, 251	{ 11	5, 8
Kansas Vebraska	7	5,010	8	Į 0,112	10	1,200	10	K .
/ichigan	168	1, 849, 622	173	2, 232, 069	{ 174 111	2, 478, 219	175 114	2, 104. 0
Visconsin	118	148	115	106	1112	86	2	۲
outh Dakota	290	7, 558, 466	285	9, 080, 242	319	11, 676, 773	325	11, 958,
Total North Central	1,057	16, 291, 065	1,061	20, 926, 271	1, 126	26, 358, 993	1, 140	26, 855, 9
Arizona	1		1	1				-
Arizona	} 1	36	î	35	2	67	2	
New Mexico	1		1 1				1	ł
	} 19	412, 220	10 7	457, 487	18	644, 393	18	666,
Ttoh	] 19	412, 220	7	J 401, 401	1	011,000	1 -0	000,
dano	l) _		1	007		870		,
Wyoming	5	308	1 3	687	4	578	5	1 '
Montana	]		l 3	)	-			ļ
Total Rocky Mountain	25	412, 564	25	458, 209	24	645, 038	25	666,
Oregon	19	1 0000	ſ 19	7 510	ſ 18	9,830	§ 17	} 17,
Washington		6,312	36	7, 519	33	IJ '	լլ օս	1)
California	95	174, 463		181,921	98	202, 328	93	255,
		-	-	100 110	140	919 159	140	272,
Total Pacific Coast	151	180, 775	148	1 189, 440	149	212, 100	140	1. 2.2,
Total Pacific Coast	151 2, 465	180, 775 35, 232, 699	====	189, 440 46, 185, 828	=	212, 158 56, 185, 472	=	59, 042,

いるとはなることできているというないというと

# WORLD PRODUCTION

The accompanying table shows the production of pig iron, by countries, from 1938 to 1942, insofar as statistics are available.

World production of pig iron (including ferro-alloys), 1938-42, by countries, in metric tons 1

[Compiled by B. B. Waldbauer]

Country 1	/ 1938	1939	1940	1941	1942
Australia 2	944, 597	1, 122, 334	(3)	(4)	(4)
Belgian Congo Belgium	5 600	5 600	5 600	(4)	(4)
Belgium	2, 426, 130	3, 058, 730	6 2, 200, 000	(4)	(4)
Brazil Canada China (Manchuria) Chosen Czechoslovakia	122, 352	160,016	185, 570	208, 795	5 208,000
Canada	773, 573	845, 461	1, 323, 128	1,579.648	1, 985, 500
China (Manchuria)	5 700,000	5 700, 000	5 700, 000	(4)	(4)
Chosen	<b>\$200,000</b>	5 200, 000	5 200, 000	(4)	(4)
Czechoslovakia	1, 233, 987	7 1,000,000	(8)	(4)	(4)
	21,000	5 30, 000	(3)	(4)	(4)
France	6,061,322	77,900,000	6 4, 600, 000	(4)	(4)
Germany 9 Austria	<b>18, 596, 000</b>	20, 300, 000	6 21, 000, 000	(4)	(4)
Hungary	350, 537	7 460, 000	(3)	(4)	(4)
India, British	1, 583, 284	1, 785, 242	2, 015, 116	(4)	(4)
Italy	928, 847	7 1,000,000	6 890, 000	(4)	( <del>4</del> )
Japan	5 2, 800, 000	5 3,000,000	6 3, 000, 000	(4)	(4)
Luxemburg	1,500,000	7 1, 800, 000	6 1,000,000	(4)	(4)
India, British Italy Japan Luxemburg Mexico	98, 376	141, 335	93, 179	108, 524	(4)
Netherlands	266, 956	284,004	(3)	(4)	(4)
Norway Poland	173, 748	190, 785	(3)	(4)	(4)
Poland	967, 668	1,000,000	(8)	(4)	(4)
Rumania	132, 681	5 140, 000	(3)	(4)	( <del>4</del> )
Spain	442, 574	473, 360	588, 076	536, 863	10 438, 072
Rumania Spain Sweden	713, 579	691, 402	787, 211	(4)	(4)
Union of South Africa	294, 406	300, 227	303, 923	(4)	11 196, 300
U. S. S. R	15, 179, 856	7 15, 200, 000	6 15, 500, 000	(4)	(4)
United Kingdom	6,871,546	7 8, 300, 000	6 8, 437, 000	(4)	(4)
United States	19, 474, 677	32, 321, 653	43, 026, 030	51, 456, 627	55, 308, 045
Yugoslavia	58, 458	61, 106	(3)	12 75, 000	(4)
	82, 923, 000	102, 466, 000	107, 882, 000	(4)	(4)

<sup>&</sup>lt;sup>1</sup> Pig iron is produced in Chile, New Zealand, and the Philippine Islands in addition to countries listed, but production figures are not available.
<sup>2</sup> Year ended June 30.

#### FERRO-ALLOYS

# PRODUCTION AND SHIPMENTS

The production of ferro-alloys in 1942 totaled 1,889,409 short tons, compared with 1,636,073 tons in 1941—an increase of 15 percent. In 1942, ferro-alloys were made at 18 blast-furnace plants, 20 electricfurnace plants, and 3 aluminothermic plants. In addition, 3 plants made ferrophosphorus, and 2 plants made ferrosilicon as a byproduct. Of the 1942 total, 1,076,328 tons were made in blast furnaces, 778,112 tons in electric furnaces, and 33,427 tons by the aluminothermic process, and 1,542 tons of alloys were produced as byproducts. ments of all classes of ferro-alloys in 1942 increased 8 percent in quantity and 26 percent in value over 1941.

<sup>2</sup> Year ended June 30.
3 Estimate included in total.
4 Data not available.
5 Estimated production.
6 Approximate production as published by The Iron Age, vol. 147, No. 1, January 2, 1941, p. 61.
7 Approximate production as published by Steel, vol. 196, No. 1, January 1940, p. 269.
8 Included in the German figure in 1940.
9 Beginning with March 1935, production of the Saar is included with that of Germany.
10 January to October, inclusive.
11 January to July, inclusive.
12 Crostic only

<sup>12</sup> Croatia only.

大学のない 大学のないのからいとう

Ferro-alloys produced and shipped from furnaces in the United States, 1941-42

		1941			1942	
Alloy	Produc- Shipments		Produc-	Shipments		
	tion (short tons)	Short tons	Value	tion (short tons)	Short tons	Value
Ferromanganese Spiegeleisen Ferrosilicon Ferrophosphorus Ferrotungsten Ferrotoron Ferrotitanium Ferrowanadium Ferromolybdenum Molybdie oxide Calcium molybdate and compounds Other varieties 3	580, 704 177, 915 618, 227 21, 824 6, 549 (1) 14, 238 22, 331 194, 285	619, 395 181, 177 661, 913 11, 821 6, 415 (1) 15, 194 23, 314 200, 556	\$69, 378, 004 5, 793, 481 34, 084, 428 749, 916 19, 056, 118 (2) (2)	661, 338 186, 026 712, 710 28, 161 7, 108 190 17, 048 41, 718 235, 110	659, 219 186, 163 707, 522 7, 761 7, 148 113 16, 823 41, 680 233, 858	\$82, 726, 298 5, 931, 728 39, 691, 636 513, 886 21, 547, 454 (2) (2) (2)
	1, 636, 073	1, 719, 785	204, 856, 619	1,889,409	1, 860, 287	257, 749, 18

1 Included with "Other varieties."

<sup>2</sup> Value included in total. <sup>2</sup> Silicomanganese, manganese briquets, ferrochromium, chrome-manganese, ferrocolumbium, and zir-conium-ferrosilicon.

Ferromanganese.—The output of ferromanganese in 1942 came from 11 blast-furnace plants and 3 electric-furnace plants compared with 10 blast-furnace plants and 3 electric plants in 1941. Of the manganese ore used in 1942, 98.6 percent was foreign ore. The ferromanganese produced in 1942 averaged 79.01 percent manganese. During 1942, steel producers used 12.4 pounds of metallic manganese as ferroalloys per ton of steel produced. Of this quantity, 11.2 pounds was in the form of ferromanganese. A total of 665,299 tons of ferromanganese was consumed in 1942—all by the iron and steel industry.

Ferromanganese produced in the United States and metalliferous materials consumed in its manufacture, 1938-42

	anganese pr	ganese produced		Materials consumed (short tons)					
Year	Short	Mang conta		percent	ese ore (35 or more atural)	Iron and manga- niferous	Cinder, scale, and pur-	used per ton of ferro- manga- nese	
t	tons	Percent	Short tons	Foreign	Domes- tic	iron ores	chased scrap	made (short tons)	
1938 1939 1940 1941 1942	272, 153 302, 524 514, 682 580, 704 661, 338	78. 65 79. 24 79. 45 79. 48 79. 01	214, 036 239, 725 408, 903 461, 539 522, 553	466, 746 563, 344 976, 332 1, 122, 187 1, 273, 596	25, 254 13, 419 9, 414 17, 572	10, 860 9, 323 5, 889 5, 166 19, 545	9,477 7,000 1 8,868 6,031 4,634	1. 808 1. 862 1. 923 1. 949 1. 952	

<sup>1</sup> Corrected figure.

Manganese ore used in manufacture of ferromanganese in the United States, 1938-42, by sources of ore

	198	8 •	193	39	194	10	194	1	194	2
Source of ore	Gross weight (short tons)	Mn con- tent, nat- ural (per- cent)	Gross weight (short tons)	Mn con- tent, nat- ural (per- cent)	Gross weight (short tons)	Mn con- tent, nat- ural (per- cent)	Gross weight (short tons)	Mn con- tent, nat- ural (per cent)	Gross weight (short tons)	Mn con- tent, nat- ural (per- cent)
Domestic Foreign: Africa Brazil Chile Cuba India Java	25, 254 171, 022 71, 747 40, 650 62, 681	53. 20 48. 99 41. 44 48. 07 49. 24	144, 734	43. 75 48. 16	189, 389 6, 076 112, 859		328, 769 4, 715 135, 581	47. 11 42. 29	274, 450 342, 538 5, 677 171, 029	39. 69 46. 61 41. 55 46. 64 46. 33 49. 75 46. 28
Mexico Philippine Islands U. S. S. R Undistributed	120, 646	47. 61	189, 628	47. 54	12, 768 187, 286 46, 505	47. 16 47. 85 38. 75		48. 32	2, 013 19, 741 64, 051	45. 31 46. 05 48. 06 45. 75
	492,000	47. 72	563. 344	47. 72	989, 751	46. 45	1, 131, 601	46. 54	1, 291, 168	45. 99

 <sup>&</sup>lt;sup>1</sup> Tonnage entered under "Undistributed" comprises ore from India and U. S. S. R.; separation as to source not reported by consumer.
 <sup>2</sup> Source of ore not reported by consumer.

Spiegeleisen.—The spiegeleisen produced in 1942 came from four blast-furnace plants, averaged 19 percent manganese, and had an average value of \$31.86 per short ton at furnaces. All spiegeleisen in 1942 was manufactured from domestic materials and was made by the Carnegie-Illinois Steel Corporation, Pittsburgh, Pa. and the New

Jersey Zinc Co., New York, N. Y.

Ferrosilicon.—Of the total of 712,710 short tons of ferrosilicon produced in 1942, 258,943 tons were produced in blast furnaces, 452,732 tons in electric furnaces, and 1,035 tons as a byproduct in the manufacture of artificial abrasives in electric furnaces. The silicon content of the production in 1942 ranged from 9 to 95 percent and averaged Blast-furnace production averaged about 10 percent 30 percent. silicon.

Ferrophosphorus.—The ferrophosphorus produced in 1942 averaged 24 percent phosphorus, and shipments were valued at \$66.21 per short

ton f. o. b. furnaces. All was made from domestic materials.

Ferrotungsten.—Production of ferrotungsten in 1942 totaled 14,216,-680 pounds (7,108 tons), averaging 79 percent tungsten. The average value at furnaces was \$1.899 per pound of contained tungsten and \$3,014 per short ton of alloy. All ferrotungsten was made in electric furnaces.

Ferrochromium.—The industrial consumers of ferrochromium re-

ported using 162,904 tons of ferrochromium during 1942.

Ferromolybdenum.—The bulk of the ferromolybdenum produced in 1942 was made by the aluminothermic process. All was produced

from domestic ores and averaged 62 percent Mo.

Molybdic oxide, calcium molybdate, and molybdenum compounds.-As these products are used as alloying agents in the production of iron and steel, they are included with ferro-alloys. These compounds averaged 80 percent Mo in 1942. They are considerably less expensive than ferromolybdenum and consequently are used to a greater extent.

Ferrovanadium.—The ferrovanadium produced in 1942 averaged 38 percent V, and the value averaged \$2.75 per pound of metal contained, at furnaces. This alloy is produced by electric and aluminothermic processes, using both foreign and domestic ores.

Silicomanganese.—The silicomanganese produced in 1942 averaged

67 percent manganese and was produced in electric furnaces.

Manganese briquets.—During 1942, manganese briquets averaged 56 percent Mn. Manganese briquets are used chiefly in the foundry

industry.

Ferrotitanium.—During 1942, the ferrotitanium produced averaged 12 percent Ti. The bulk was made in electric furnaces, but some was produced by the aluminothermic process. Both foreign and domestic ores were consumed in the manufacture of ferrotitanium in 1942. Ferrotitanium is used chiefly as a deoxidizer and scavenger in steel making and is also valuable as an alloying agent in certain steels to prevent intergranular corrosion.

Ferroboron.—One hundred and ninety short tons of ferroboron containing 8 percent B were produced in 1942. Boron finds its main use

in special steels as a hardening agent.

Ferrocolumbium.—Columbium additions have a valuable use in preventing intergranular corrosion. The production in 1942 averaged

57 percent Cb.

Zirconium-ferrosilicon.—The zirconium-ferrosilicon produced in 1942 averaged 14 percent Zr. Zirconium is a powerful deoxidizer and scavenger and reduces age hardening, thereby improving deep drawing properties of sheet steel.

#### FOREIGN TRADE

Imports and exports of the rarer metals are not recorded separately but are grouped as shown in the accompanying tables. Ferromanganese and spiegeleisen comprised most of the imports in both 1941 and 1942.

Ferro-alloys and ferro-alloy metals imported for consumption in the United States, 1941-42, by varieties

		1941			1942	
-Variety of alloy	Gross weight (short tons)	Content (short tons)	Value	Gross weight (short tons)	Content (short tons)	Value
Ferromanganese: Containing over 1 percent carbon Containing not over 1 percent carbon. Manganese boron, manganese metal, and	7, 017 15	5, 683 13	\$555, 553 1, 597	14, 772	11, 617	\$1, 274, 749
spiegeleisen not more than 1 percent carbon (manganese content)	(¹) 4, 741	(¹)	12, 405 215, 108	(¹) 1,990	(¹) 5	2, 220 95, 853
Containing 3 percent or more carbon_ Containing less than 3 percent carbon_	138	88	19, 242	9 514	5 436	1, 598 185, 963
Ferrosilicon	18, 261	6, 190	750, 975	15, 211	4, 394	569, 134
Chromium and zirconium silicon and calcium silicide	56	(1)	8, 337	30	(1)	10, 144
grains, or powder: Tungsten metal (tungsten content)	(1)	18	48, 307	(1)	2	7, 668

<sup>1</sup> Not recorded.

Ferromanganese and ferrosilicon imported for consumption in the United States, 1941-42, by countries

	Ferrom	Ferromanganese (manganese content)				Ferrosilicon (silicon content)			
Country	1941		1942		1941		1942		
	Short	Value	Short tons	Value	Short tons	Value	Short tons	Value	
Canada Norway United Kingdom	1, 202 13 4, 481	\$136, 029 1, 597 419, 524	5, 022 6, 595	\$654, 219 620, 530	6, 190	\$750, 975	4, 394	\$569, 134	
	5, 696	557, 150	11, 617	1, 274, 749	6, 190	750, 975	4, 394	569, 134	

Ferro-alloys and ferro-alloy metals exported from the United States, 1941-42, by varieties

	1941		19	1942	
Variety of alloy	Short tons	Value	Short tons	Value	
Ferromanganese and spiegeleisen Other ferro-alloys 1	5, 155 18, 908	\$771, 575 5, 029, 802	7, 223 14, 653	\$979, 113 6, 464, 810	

<sup>1</sup> Includes ferrosilicon, ferrotungsten, ferrovanadium, and other ferro-alloys.

#### STEEL

#### GENERAL FEATURES

Steel production continued at a high rate throughout 1942, furnaces operating at an average of 97 percent of capacity for the year. Capacity for producing steel increased 1,723,000 short tons to reach a new record total of 90,293,000 tons. The data concerning steel operations used by the Bureau of Mines are furnished by the American Iron and Steel Institute. Not included in the statistics is the output from steel foundries that do not produce steel ingots. During 1942 the Bureau of Mines obtained some information to determine the magnitude of this tonnage. There are, in all, about 275 plants producing steel ingots and castings in the United States. In addition to the output of steel shown in the following table, 756,884 tons of basic open hearth and 228,630 tons of basic electric steel were produced for castings. Not known for 1942 is the quantity of bessemer steel, acid open-hearth steel, and acid electric steel produced by independent foundries that produce only castings. This quantity is relatively very small.

Steel capacity, production and percent of operations, 1896-1942, in short tons 1 [Ingots and steel for castings 2]

				Production	•		
Years	Capacity	Open hearth	Bessemer	Crucible	Electric and all other	Total	Percent capacit
896	13, 441, 680	1, 454, 544	4, 390, 295	67, 972	2, 681	5, 915, 492	44
897	(*)	1,801,712	6, 132, 353	78, 354	3, 373	8, 015, 792	(*
897 898	(*) 15, 869, 560	2, 497, 927	7, 402, 099	100.517	4, 257	10, 004, 800	63
899	(*)	3, 300, 994	8, 496, 716	113, 359	5, 571	11, 916, 640	
900	·	3, 805, 911	7, 486, 942	112, 629	5, 446		3
901	(*) 24, 039, 064	5, 215, 066	9, 758, 898	110, 335		11, 410, 928	62
902	24, 000, 004 (*)	6, 370, 256	10, 234, 967		6, 127	15, 090, 426	
002	*	6, 529, 500		126, 305	9, 392	16, 740, 920	(,
903	28, 213, 147	6 617 146	9, 623, 968	114, 726	10, 981	16, 279, 175	$\Gamma$
704	28, 213, 147	6, 617, 146	8, 802, 237	93, 398	10, 293	15, 523, 074	55
100	(‡)	10, 047, 941	12, 254, 340	114, 501	10,039	22, 426, 821	(
06	(1)	12, 298, 063	13, 748, 930	142, 815	16, 105	26, 205, 913	(
07	(*)	12, 935, 704	13, 067, 655	146, 982	15, 764	26, 166, 105	(1
008	38, 237, 343	8, 777, 136	6, 850, 766	71, 267	6, 868	15, 706, 037	4
09	(*)	16, 233, 208	10, 450, 477	120, 238	25, 701	26, 829, 624	(
10	(*)	18, 485, 050	10, 542, 305	136, 979	61, 975	29, 226, 309	(
11	(*)	17, 470, 488	8, 901, 596	109, 371	35, 783	26, 517, 238	Ċ
12	(*)	23, 274, 410	11, 567, 249	136, 099	23, 701	35, 001, 459	l è
13	(*)	24, 191, 923	10, 691, 191	135, 773	38, 092	35, 056, 979	1 ?
14	44, 451, 977	19, 235, 646	6, 967, 348	100,653	30, 947	26, 334, 594	Š
15	46, 249, 146	26, 520, 594	9, 281, 679	127, 436	79, 452	36, 009, 161	7
16	51, 282, 314	35, 185, 278	12, 386, 124	145, 255	189, 865	47, 906, 522	9
17	55, 567, 555	38, 246, 760	11, 737, 555	141, 922	341, 643	50, 467, 880	9
18	58, 846, 418	38, 594, 518	10, 501, 384	128, 925	573, 096	49, 797, 923	8
19	61,020,669	30, 182, 537	8, 144, 149	71, 201	433, 892	38, 831, 779	6
20	62, 313, 591	36, 592, 522	9, 949, 057	80, 937	566, 370	47, 188, 886	7
21	64, 262, 027	17, 460, 578	4, 497, 851	8, 527	190, 897	22, 157, 853	3
22	65, 426, 682	32, 826, 061	6, 629, 614	32, 039	387, 563	39, 875, 277	6
23	65, 682, 014	40, 207, 616	9, 502, 179	49, 368	577, 777	50, 336, 940	7
24	66, 563, 515	35, 366, 632	6, 607, 541	25, 170	484, 429	42, 483, 772	6
25	68, 473, 222	42, 598, 627	7, 530, 837	21, 910	689, 373	50, 840, 747	7
26	64, 750, 035	45, 575, 016	7, 766, 716	17, 352	729, 930	54, 089, 014	8
27	67, 236, 117	42, 636, 535	6, 934, 734		746, 018		
28	68, 840, 912	49, 407, 631		10, 120	740, 018	50, 327, 407	7
29	71, 438, 516		7, 414, 618	8, 701	898, 531	57, 729, 481	8
30		54, 155, 235	7, 977, 210	7, 442	1,065,603	63, 205, 490	8
00	72, 985, 406	39, 255, 073	5, 639, 714	2, 523	686, 111	45, 583, 421	6
31 32	77, 257, 803	25, 210, 714	3, 386, 259	1, 733	460, 255	29, 058, 961	3
02	78, 780, 913	13, 336, 210	1, 715, 925	722	270, 044	15, 322, 901	1
33	78, 614, 403	22, 827, 473	2, 720, 246	763	471,747	26, 020, 229	3
34	78, 128, 416	26, 354, 838	2, 421, 840	595	404, 651	29, 181, 924	3
35	78, 451, 930	34, 401, 280	3, 175, 235	719	606, 471	38, 183, 705	4
36	78, 164, 300	48, 760, 463	3, 873, 472	914	865, 150	53, 499, 999	6
37	78, 148, 374	51, 824, 979	3, 863, 918	1,046	947, 002	56, 636, 945	7:
38	80, 185, 638	29, 080, 016	2, 106, 340	-7	565, 627	31, 751, 990	39
39	81, 828, 958	48, 409, 800	3, 358, 916	931	1,029,067	52, 798, 714	6
40	81, 619, 496	61, 573, 083	3, 708, 573	1,024	1,700,006	66, 982, 686	8
41	<sup>3</sup> 85, 158, 150	74, 389, 619	5, 578, 071	2, 313	2, 869, 256	82, 839, 259	9
42	4 90, 293, 000	76, 501, 957	5, 553, 424	2,010	3, 974, 540	86, 031, 931	) 96

#### Open-hearth steel ingots and castings manufactured in the United States, 1938-42, by States, in short tons

[Includes only that portion of steel for castings produced in foundries operated by companies manufacturing steel ingots]

State	1938	1939	1940	1941	1942
New England States	183, 297 1, 509, 538 7, 920, 816 6, 016, 902 3, 847, 603 2, 184, 251 7, 417, 609	286, 850 2, 627, 910 13, 622, 272 9, 913, 454 6, 486, 502 3, 687, 874 11, 784, 938	322, 753 3, 618, 444 18, 469, 170 11, 769, 780 8, 421, 956 4, 963, 457 14, 007, 523	462, 754 4, 232, 521 23, 007, 147 14, 746, 523 10, 366, 380 5, 998, 679 15, 575, 615	472, 521 4, 378, 808 23, 562, 866 14, 769, 085 10, 578, 989 6, 335, 946 16, 403, 742
	29, 080, 016	48, 409, 800	61, 573, 083	74, 389, 619	76, 501, 957

American Iron and Steel Institute.
 The figures for 1934 and subsequent years include only that portion of the capacity and production of steel for castings used by foundries which were operated by companies producing steel ingots.
 Figures not available.
 Average annual capacity as of January 1 and July 1, 1941.
 Annual capacity as of January 1, 1943.

TO ACCUMENT OF THE PARTY OF THE

Bessemer-steel ingots and castings manufactured in the United States, 1938-42, by States, in short tons

[Includes only that portion of steel for castings produced in foundries operated by companies manufacturing steel ingots]

State	1938	1939	1940	1941	1942
Ohio	1, 202, 916 389, 827 513, 597	1, 439, 629 1, 109, 081 810, 206	1, 459, 807 1, 366, 017 882, 749	2, 265, 987 1, 966, 779 1, 345, 305	2, 250, 717 1, 997, 547 1, 305, 160
	2, 106, 340	3, 358, 916	3, 708, 573	5, 578, 071	5, 553, 424

Steel electrically manufactured in the United States, 1938-42. in short tons
[Includes only that portion of steel for castings produced in foundries operated by companies manufacturing steel ingots]

Year	Ingots	Castings	Total	Year	Ingots	Castings	Total
1938 1939 1940	524, 843 951, 522 1, 608, 032	40, 784 77, 545 91, 974	565, 627 1, 029, 067 1, 700, 006	1941 1942	2, 758, 611 3, 843, 757	110, 645 130, 783	2, 869, 256 3, 974, 540

The steel output for 1942 includes 11,526,374 short tons of alloysteel ingots and castings, which represent 13 percent of the total. This figure includes steels in which the minimum of the range specified in any of the elements named exceeds the following percentages: Nickel, 0.40 percent; chromium, 0.30 percent; copper, 0.50 percent; manganese, 1.65 percent; silicon, 0.50 percent; molybdenum, 0.10 percent; vanadium, tungsten, cobalt, titanium, and zirconium, any percentage. The output of alloy steels in 1942 increased 40 percent and that of total steel 4 percent over 1941. Of the total alloy-steel output in 1942, 65 percent came from basic open hearths, 5 percent from acid open hearths, 30 percent from electric furnaces, 522 tons from crucible furnaces, and none from bessemer converters.

Production of alloy-steel ingots and castings, 1938-42, by processes, in short tons
[Includes only that portion of steel for castings produced in foundries operated by companies manufacturing steel ingots]

Process	1938	1939	1940	1941	1942
Open hearth, basic	1, 179, 031 102, 089 13 5 372, 372	2, 302, 273 156, 581 3, 486 231 749, 384	3, 421, 961 252, 965 3, 990 255 1, 286, 716	1 5, 306, 415 433, 240 3, 890 933 2, 461, 651	7, 524, 209 608, 867 522 3, 392, 776
•	1, 653, 510	3, 211, 955	4, 965, 887	1 8, 206, 129	11, 526, 374

<sup>&</sup>lt;sup>1</sup> Revised figures.

From the accompanying tables it will be seen that most of the steel made in electric furnaces (85 percent in 1942) is alloy steel. Typically, steels with higher alloy content are made in electric furnaces and steels with lower alloy content by the open-hearth process.

# FOREIGN TRADE

Imports and exports of iron and steel products are given in detail in the following tables:


Iron and steel imported for consumption in the United States, 1941-42, by commodities

	194	1	1942 1		
Commodity	Short tons	Value	Short tons	Value	
Semimanufactures:					
Steel bars: Concrete reinforcement	6	\$321	2	\$442	
G 114 bollow n o s	603	67,060	437	67, 489	
Hollow and hollow drill steel	250	34, 897	1	253	
Hollow and hollow drill steel	17	1,671	1	324	
Bar iron		-,	esta les Tal		
Wire rods, nall rods, and nat rods up to o menes m	119	36, 699	57	14, 165	
width	73	15, 977	226	24, 579	
Boiler and other plate iron and steel, n. e. s	3, 939	593, 454	6,882	184, 260	
Steel ingots, blooms, and slabs	181	15, 227	281	34, 609	
Dillota polid or bollow		7, 623	54	13, 264	
Die blocks or blanks; shatting, etc	53	10, 679	28	7, 234	
	122	31, 330	117	27, 945	
Tin plate, terneplate, and tagger's tin	122	31, 330	11.	21,010	
	0577	50, 927	141	9, 406	
Structural iron and steel	357		14. 431	426, 607	
Rails for railways	7,672	200, 796	14, 401	420,00	
Pipes and tubes:		- 00		729	
Pipes and tubes: Cast-iron pipe and fittings Other pipes and tubes	1	166	628	85, 743	
Other pines and tubes	1, 224	140, 545	028	80, 740	
Wire:			(0)		
Barbed	(2)	21	(2)	10 10	
Deserted region on a c	39	9, 426	89	10, 187	
Telegraph, telephone, etc., except copper, cov-				10.00	
ared with cotton 111th etc	27	12,005	44	19,06	
Flat and steel strips not thicker than 14-inch				407.00	
and not over 16 inches wide	2,605	1, 540, 627	210	185, 89	
Rope and strand	105	21, 823	36	9, 33	
Colmonized foncing wire and wire fencing	1	70	(3)	(3)	
Hoop, band, or scroll iron or steel	1		1	23:	
noop, pand, or seron non or secon	31	9, 262	229	11,08	
Nails		79, 311	450	182, 79	
Castings and forgings, n. e. s.	000	137.5	4 1 2 1 1 1 1		

 <sup>1</sup> January to November, inclusive; December figures not available at time of publication.
 2 Less than 1 ton.
 3 Not available at time of publication.

# Iron and steel exported from the United States, 1941-42

Article	19	941	1942		
Article	Short tons	Value	Short tons	Value	
Semimanufactures:					
Steel ingots, blooms, billets, slabs, and sheet bars Iron and steel bars and rods:	2, 314, 478	\$95, 844, 101	2, 846, 958	\$92, 344, 86	
Iron bars	7, 261	743, 554	5, 098	532, 68	
Concrete reinforcement bars	170, 368	9, 589, 930 44, 383, 014	74, 917	4, 490, 18	
Iron bars. Concrete reinforcement bars. Other steel bars.	409, 664	44, 383, 014	556, 842	74, 417, 96	
Other steel bars. Wire rods. Iron and steel plates, sheets, skelp, and strips: Boiler plates. Other plates, not fabricated. Skelp iron or steel. Iron and steel sheets, galvanized. Steel sheets, black, ungalvanized. Iron sheets, black. Strip band, and scroll iron or steel: Cold-rolled.	187, 326	9, 385, 027	145, 251	7, 497, 76	
Roller plates, sheets, skelp, and strips:	26 000	1 220 010	90 010	9 001 70	
Other plates not fabricated	26, 998 378, 171	1, 330, 018	38, 818	2, 091, 79 27, 222, 39 7, 662, 71	
Skeln iron or steel	162 524	22, 649, 187 6, 973, 459 10, 561, 058	402, 568 170, 876	7 662 71	
Iron and steel sheets, galvanized	162, 524 118, 988	10, 561, 058	100, 411	8 022 47	
Steel sheets, black, ungalvanized	480, 078	34, 474, 539	795, 380	8, 022, 47 57, 317, 34	
Iron sheets, black	24, 553	2, 141, 216	14, 940	1, 120, 43	
Strip band, and scroll iron or steel:	2.5				
Cold-rolled	71, 618 107, 322 397, 532	7, 843, 042 7, 020, 080 42, 835, 146	129, 169 92, 855 665, 387	18, 547, 06 6, 932, 48 70, 697, 15	
Hot-rolled	107, 322	7, 020, 080	92, 855	6, 932, 48	
Hot-rolled	397, 532	42, 835, 146	665, 387	70, 697, 15	
Manufactures—steel-mili products:					
Structural iron and steel:	4.5	100		1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	
Water, oil, gas, and other storage tanks com- plete and knocked-down material	21,775	2, 127, 604	07.045	2 210 60	
Structural shapes:	21,773	2, 127, 004	27, 945	3, 319, 68	
Not fabricated	295, 025	14 705 406	101 197	0 319 19	
Not fabricated Fabricated Plates fabricated, punched, or shaped	56 820	14, 795, 406 5, 691, 559	191, 127 33, 236	9, 318, 12 3, 994, 37	
Plates fabricated, punched, or shaped	56, 820 25, 392	2, 250, 925	12, 699	1, 352, 38	
Metal lath	3, 282	556, 857	1, 156	198, 30	
Metal lathFrames, sashes, and sheet piling	10, 111	876, 533	4, 238	443, 52	
Railway track material:	,			, 0	
Raile for railwaye	169, 542	7, 205, 850	299, 394	11, 514, 65	
Rail joints, splice bars, fishplates, and tie plates	19, 423 2, 334	1, 254, 491	31, 586	2, 126, 53	
Switches, frogs, and crossings	2, 334	350, 420	13, 297	1, 634, 29	
Railroad spikesRailroad bolts, nuts, washers, and nut locks	7,724	7, 205, 850 1, 254, 491 350, 420 605, 934	299, 394 31, 586 13, 297 6, 854	1, 634, 29 515, 93	
Railroad bolts, nuts, washers, and nut locks	2, 481	434, 920	3, 751	649, 04	
Tubular products:					
Boiler tubes. Casing and oil-line pipe Seamless black pipe, other than casing and oil	53, 518 141, 947	7, 443, 724 11, 857, 884	30, 320	4, 474, 47	
Casing and on-line pipe	141, 947	11,807,884	136, 826	12, 299, 54	
line	45, 806	E 740 670	21 997	7 100 24	
Welded black nine	86, 246	5, 749, 670 7, 917, 243	61, 287 116, 014 42, 775	7, 122, 36 10, 708, 50 4, 329, 73	
Welded galvanized pine	80, 505	7, 554, 467	42 775	4 329 73	
Malleable-iron screwed pipe fittings	5, 707	1, 768, 090	5, 024	1, 893, 84	
Cast-iron screwed pipe fittings	5, 707 1, 344	i 226 AAQ	1 430	368, 85	
Cast-iron pressure pipe and fittings	43, 638	2, 578, 515	16,008	1, 246, 85	
Cast-iron soil pipe and fittings	18, 410 34, 884	1, 106, 988	5, 727	460, 66	
Welded black pipe Welded galvanized pipe Welded galvanized pipe Malleable-iron screwed pipe fittings Cast-iron screwed pipe fittings Cast-iron pressure pipe and fittings. Cast-iron soil pipe and fittings. Riveted-steel or iron pipe and fittings	34, 884	2, 578, 515 1, 106, 988 7, 306, 724	16, 008 5, 727 115, 849	19, 076, 21	
wire and manuactures:					
Barbed	79, 422	6, 403, 041	162, 344	13, 137, 74	
Galvanized wire	63, 649	5, 810, 095	79, 988	7, 949, 67	
iron or steel wire, uncoated	79, 740	7, 805, 269	69, 172	9, 261, 51	
Galvanized wire.  Iron or steel wire, uncoated.  Wire rope, and strand.  Woven-wire fencing and screen cloth.  All other.  Nails and bolts (except railroad):  Wire nails	22, 595	7, 268, 137 3, 183, 111 5, 017, 934	37, 062 7, 237 27, 728	14, 384, 07 2, 330, 32	
W OVER-wire lending and screen cloth	11, 301	3, 183, 111	7, 237	2, 330, 32	
Noile and holte (except reilroad)	27, 429	0, 017, 934	21,120	8, 065, 20	
Nails and bolts (except railroad): Wire nails. Horseshoe nails. All other nails, including tacks and staples	56, 808	4, 510, 235	23, 907	2, 219, 28	
Horseshoe nails	3, 130	709, 698	795	202, 36	
All other nails, including tacks and staples Bolts, nuts, rivets, and washers (except rail- road)	10, 229	6, 825, 278	7, 070	1, 085, 10	
Bolts, nuts, rivets, and washers (except rail-	20, 220	0,020,210	1,010	1, 000, 10	
road)	49, 720	11, 519, 039	33, 646	9, 884, 37	
Castings and forgings:	• •		-,		
Horseshoes and calks	851	107, 168 30, 047, 323	71	12, 19	
Iron and steel, including car wheels and axles	134, 059	30, 047, 323	161, 667	40, 638, 01	
dvanced manufactures:		i			
House heating boilers and radiatorsOil burners and parts		536, 189		370, 92	
Oil purners and parts.		1, 402, 318		989, 98	
Tools:		F04 450			
Axes.		704, 476		514, 67	
SHOVEIS AND SPACES		667, 863		570.36	
Axes Shovels and spades Hammers and hatchets Saws, wood and metal cutting All other tools		704, 476 667, 863 661, 987 4, 155, 793 25, 627, 925		443, 10 5, 797, 41 49, 665, 54	
baws, wood and metal cutting		4, 155, 793		5, 797, 41	
		1 20, 027, 925		49, 005, 54	



# MANGANESE AND MANGANIFEROUS ORES

By Norwood B. Melcher 1

#### SUMMARY OUTLINE

	Page	물레이를 잡으면 하는 데 뭐가 하고 있는 것이다.	Page
General perspective	613	Metallurgical industry—Continued.	
Salient statistics	614	Spiegeleisen	626
Government purchases	615	Manganiferous pig iron	627
Domestic production	616	Battery industry	627
Imports of manganese ore	621	Miscellaneous industries	627
Consumption and stocks of manganiferous raw	3.5	Prices	628
materials	622	Ferromanganese	628
Metallurgical industry	623	Manganese ore	628
Ferromanganese	623	World production	629

#### GENERAL PERSPECTIVE

The unprecedented demand for manganese by the steel industry resulted in a record consumption of manganese ore during 1942. Domestic production (shipments from domestic mines) in 1942, stimulated by higher prices, more than doubled the 1941 output and totaled 190,748 short tons; in 1941 shipments amounted to 87,794 short tons. In addition, 268,764 short tons of ore containing 10 to 35 percent manganese and 1,500,613 short tons of ore containing 5 to

10 percent manganese were shipped during 1942.

Although imports declined 15 percent in 1942, total domestic stocks decreased less than 1 percent and at the end of 1942 were sufficient to last at least 18 months. Because of the favorable continuation of imports during the war and the large stocks, much of the domestic expansion program outlined by the Bureau of Mines before 1942 has been deferred in favor of more critical raw-material programs. ever, at the close of 1942 low-grade ores were being stock-piled by the Government for concentrating purposes, and stocks of such ore totaled 298,973 short tons (dry). The bulk of the ore is near Las Vegas, Nev., and in the Butte-Philipsburg area of Montana. Using these ores, the Manganese Ore Co. will produce 100,000 tons of ore annually from the Las Vegas operation, and the Domestic Manganese Co. will produce about 24,000 tons of concentrate from its mill at Butte. These operations are described in detail in this chapter in the section on Domestic Production.

Since the outbreak of war in Europe in 1939, the Bureau of Mines normal program of manganese research has been greatly expedited. By authorization of the Congress, Bureau of Mines and Geological Survey engineers intensified their search for domestic deposits containing manganese and other strategic minerals. In the fall of 1940 a \$2,000,000 appropriation was made available to the Bureau for constructing and operating pilot plants to beneficiate low-grade manganese ores, to produce metallic manganese from these ores, and to develop

A CONTRACTOR OF THE PARTY OF TH

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

manganiferous deposits. Since 1939 the Bureau has engaged in 37 projects for manganese exploration, has completed 34 of them, and still is working on three. In some projects a number of ore deposits were examined. As a result of this exploration, the estimated reserves of usable manganese ore in the United States have been increased several million tons. The Bureau of Mines believes that application of available processing methods to known ores can make the United States self-sufficient in manganese should imports decline to a point requiring the development of high-cost domestic production.

The electrolytic process, invented and developed by Bureau engineers between 1935 and 1938, extracts high-grade metallic manganese from low-grade ores through leaching and electrolysis. The process, patented and assigned to the United States Government through the Secretary of the Interior, is being used in a commercial plant at Knoxville, Tenn., as well as in the Bureau of Mines pilot plant at Boulder City, Nev.

Several shipments of 99.9-percent manganese from the Boulder City pilot plant have been sent to branches of the Mint at Philadelphia and San Francisco. Bureau metallurgists determined that several alloys using manganese have the physical and chemical properties required as a substitute for the 5-cent coin heretofore made of 75-percent copper and 25-percent nickel. The new coin, containing 9 percent manganese, 35 percent silver, and 56 percent copper, closely approximates the old coin in hardness, appearance, durability, and electrical resistance and may be used in coin-operated machines. Some attempts have been made to substitute less pure manganese, but the results have been unsatisfactory. By eliminating all the nickel formerly used in 5-cent coins, the adoption of the new alloy is releasing approximately 450 tons of this scarce metal and 250 to 350 tons of copper annually for the manufacture of war materials and essential civilian goods.

Salient statistics of the manganese industry in the United States, 1925-29 (average) and 1938-42, in short tons

	1925–29 (average)	1938	1939	1940	1941	1942 .
Manganese ore: Total shipments containing 35 percent or more Mn. Shipments of metallurgical ore. Shipments of battery ore. Imports for consumption. Ferro-alloys: Production of ferromanganese. Imports of ferromanganese 2 3 Production of spiegeleisen. Imports of spiegeleisen 2 Exports of spiegeleisen and ferromanganese.	66, 429  1 46, 919 19, 510 672, 000 343, 123 4 56, 661 106, 919 8, 174 4, 221	28, 359 19, 027 5, 554 541, 616 272, 153 23, 652 12, 668 19, 318	32, 824 20, 810 8, 699 702, 384 302, 524 37, 424 102, 470 42, 856 3, 274	44, 936 30, 416 10, 383 1, 435, 928 514, 682 9, 601 114, 119 17, 455 14, 600	87, 794 73, 852 11, 399 1, 714, 581 580, 704 5, 696 177, 915 4, 741 5, 155	190, 748 177, 966 12, 377 1, 560, 940 661, 338 11, 617 186, 026 1, 990 7, 223

<sup>&</sup>lt;sup>1</sup> Includes small quantity of miscellaneous ore.

<sup>&</sup>lt;sup>2</sup> Imports for consumption. <sup>3</sup> Manganese content.

Includes small quantity of other manganese alloys.

これを見るののは、一日本の様にこれです。 しょくこう




FIGURE 1.—Imports and domestic production (mine shipments) of manganese ore, 1900–1942. Statistics on imports shown in the graph represent general imports for 1900–1933, imports for consumption adjusted for changes in bonded warehouse stocks for 1934–39, and general imports for 1940–42.

Government purchases.—Government purchases of manganese ore proceeded at a high rate in 1942. The Metals Reserve Co. continued to purchase and stock-pile contract manganese ore during 1942, and on December 28, 1942, stock piles in 13 States (chiefly Maryland and Pennsylvania) contained 741,295 short tons of foreign ores and 147,558 short tons of domestic ores. The company also stock-piled noncontract manganese ore at 15 small-purchase depots, and on January 1, 1943, these piles contained 4,875 short tons of domestic ore. Purchases of low-grade ores for future milling increased greatly in 1942 and at the end of the year amounted to 298,973 short tons; most of the low-grade ore was held at Las Vegas, Nev., and at Butte, Mont.

# DOMESTIC PRODUCTION 2

The following table shows the various types of manganiferous materials shipped by domestic producers from 1938 to 1942.

Manganiferous raw materials shipped by producers in the United States, 1938-42, in short tons

		Metallı	ırgical ore		100	
Year	Manganese ore (35 per- cent or more Mn)	Ferruginous manganese ore (10 to 35 percent Mn)	Manganifer- ous iron ore (5 to 10 per- cent Mn)	Manganiferous zinc residuum	Battery ore	Miscellane- ous manga- nese ore
1938 1939 1940 1941 1942	19, 027 20, 810 30, 416 73, 852 177, 966	37, 655 268, 289 358, 406 512, 162 265, 663	308, 269 526, 067 914, 526 918, 725 1, 500, 613	43, 768 144, 747 172, 990 282, 049 292, 051	5, 554 8, 699 10, 383 11, 399 15, 410	3, 778 3, 315 4, 137 2, 543 473

Shipments of the various grades of manganese ores during the last 5 years are given, by States, in the following tables. In addition, battery-grade ores were produced in California and Montana; miscellaneous ores came from Alabama, Georgia, Montana, and Virginia; and manganiferous zinc residuum was produced from New Jersey zinc ores.

Metallurgical manganese ore shipped from mines in the United States, 1938–42, by States, in short tons

			40.00							1 1 25 5	
State	1938	1939	1940	1941	1942	State	1938	1939	1940	1941	1942
Alabama	124		348	990	26 2, 946	New Mexico North Carolina_	627	380 48	50	35	1, 267
Arkansas California Colorado	3, 345	6,009	6, 808 177 251	2,600 190	10, 112	Pennsylvania South Dakota Tennessee Utah	4,035	8, 183 56	7,821		2; 8; 2, 24; 97(
Oklahoma Oregon Georgia Idaho	3, 425	2, 964	4,001	40 - 85 4, 893 34		Virginia Washington West Virginia	1,472	532 11		4, 983 1, 588	11,02 10,66
Missouri Montana Nevada	5, 936	2, 512	9, 218 235	12 43, 555 2, 937	239 120, 409 6, 112			20, 810			
	1	1.		1 4 4 4		La transfer and the	1	1	1	1	

Ferruginous manganese ore shipped from mines in the United States, 1938-42, by States, in short tons

$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$												
$ \begin{array}{c ccccccccccccccccccccccccccccccccccc$	State	1938	1939	1940	1941	1942	State	1938	1939	1940	1941	1942
	Arizona Arkansas California Colorado New Mexico Georgia Idaho Massachusetts Michigan	3, 894 734 6, 824 3, 144 258	2, 206 8, 418 35, 839 8, 015 183 727 204, 131	1, 204 97 3, 699 41, 255 11, 298 351 2, 128 278, 580	3, 381 464 65, 483 6, 715 390 4, 480	14, 067 4, 659 89, 053 10, 514 3, 301 34, 643 88, 509	N. Carolina Oklahoma Tennessee Texas Utah Virginia Washington W. Virginia	1,870	329 293 5, 134	2, 606 2, 354 5, 020	174 56 1,865 551 4,375 7 448	916 142 78 3, 905

<sup>&</sup>lt;sup>2</sup> Throughout chapter, unless otherwise indicated, percentages expressing manganese content of ores refer to ores in natural (undried) state.

Manganiferous iron ore shipped from mines in the United States, 1938-42, by States, in short tons

State	1938	1939	1940	1941	1942
Alabama					162
Georgia Michigan	17 004		230	1, 192	
MinnesotaVirginia	17, 984 290, 285	526, 067	20, 851 893, 359 86	917, 533	1, 500, 451
	308, 269	526, 067	914, 526	918, 725	1, 500, 613

Manganese and manganiferous ores shipped from mines in the United States in 1942, by States

	Oı		ining 35 nore M	percent n	Oı	re conta	ining cent N	10 to 35 In	Oı	re contain	ing 5 to Mn	10 percent
		Short	tons			Short	tons			Short	tons	
	Shippers	Gross weight	Manganese content	Value	Shippers	Gross weight	Manganese content	Value	Shippers	Gross weight	Manganese content	Value
Metallurgical: Alabama Arizona Arizona Arkansas California Colorado Georgia Massachusetts Michigan Minnesota: Missouri Montana Newada New Mexico Oklahoma Oregon Pennsylvania South Dakota Tennessee Texas Utah Virginia Washington West Virginia Undistributed i	1 14 7 7 3 2 5 1 4 1 0 1 4 2 2 3 4 4 1 1 1 1 9 4 4 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	26 2, 946 4, 132 10, 112 (1) 4, 890 6, 112 1, 267 (1) (1) (2) 81 2, 247 970 11, 024 11, 0660 2, 240	10 1, 200 1, 409 4, 479 (1) 1, 887 72, 396 2, 168 547 (1) (1) 8 8 8 96 4, 278 4, 278 8, 389 8, 389 8, 389 216	\$73, 579 113, 678	1 9 2 1 5 10 1 1 1 2 2 1 2 2 1 5 5 1 1 1 1 5 1 1 1 1	174 14, 067 1, 670 10, 478 3, 301 34, 643 88, 509 15, 468 2, 743 89, 009 142 78 3, 905	2, 931 412 2, 847 640 4, 542 13, 401 4, 105 850 11, 377	(1) \$87, 576 13, 641 98, 827 (1) (1) (1) (1) (1) (1) (1) (1) (1) (1)	7	1,500,451	119,616	<sup>2</sup> \$3,384,654
Total metal- lurgical	101	177, 966	96, 224	5, 964, 655	43	265, 663	42, 207	1, 429, 477	8	1, 500, 613	119, 624	3, 384, 654
Battery: California Montana	3 5 2		1, 147 4, 143	518, 123	{ 6	3, 033	853	(7)				
Total battery.	7	12, 377	5, 290	518, 123	6	3, 033	853	(7)				
Miscellaneous: Alabama Georgia Montana Virginia	41 41 416	27 156 222	9 57 84	} 10,896	51 {*1 	· 32 36	9	8				
Total miscel- laneous	18	405	150	10, 896	2	68	18	(7)				
Grand total	117	190, 748	101, 664	6, 493, 674	50	268, 764	43, 078	1, 481, 948	8	1, 500, 613	119,624	3, 384, 654

<sup>1</sup> Included under "Undistributed."
2 Value for Alabama included with Minnesota.
3 2 producers in California shipped both metallurgical and battery ore.
4 1 producer in Georgia, 1 in Montana, and 5 in Virginia shipped both metallurgical and miscellaneous ore.
5 1 producer in Georgia shipped both metallurgical and miscellaneous ore.
6 Includes entries indicated by "(1)" above.
7 Value included in grand total.

Alabama.—Only one shipment of metallurgical-grade manganese ore was made from Alabama during 1942; it came from the Cobalt Hill mine in Cherokee County. In addition, a small quantity of miscellaneous-grade ore containing less than 35 percent manganese was shipped from Etowah County during the year, and some ferruginous ore came from Calhoun County.

A study of the concentration of manganese-bearing ores from Walnut Grove, Ala., has been made by Johnston, Fine, and Shelton.3

Arizona.—A total of 2,946 short tons of metallurgical ore was shipped from mines in Arizona during 1942. The largest producer was the Black Warrior mine in the Artillery Peak district. Ship-The largest producer ments from this mine were made to the Metals Reserve Co. and totaled 543 short tons. Other shipments of considerable size came from Coconino and Gila Counties. Fourteen shippers supplied the State total in 1942.

Arkansas.—The effect of the price ceiling was hard-felt in Arkansas tring 1942. Production of manganese ore dropped to 4,132 short during 1942. tons from 5.015 short tons in 1941. The operators could not pay for assaying before shipping and could not ship without knowing what the impurity penalty would be. Consequently, shipments of ferruginous manganese ore increased greatly from 3,381 short tons in 1941 to 14,067 short tons in 1942. In addition, 8,014 short tons of ferruginous manganese ore were shipped from mines to Government stock piles for later concentration. The ferruginous manganese ore in the Batesville stock pile on January 1, 1943, totaled 12,672 short tons (dry)

averaging 26.45 percent manganese.

A study of the beneficiation of wad ore from the Ayedalotte property at Batesville has been made by Shelton, Fine, and Fisher.4

California.—Twenty-eight shippers from 17 counties supplied the total of 10,112 short tons of metallurgical ore and 2,856 short tons of battery ore containing 35 percent or more (natural) manganese. Among the larger producing mines in 1942 were the Whedon mines in Imperial County, the Pine Ridge, Barker, and Jones (Black Wonder) mines in Santa Clara County, the Buckeye and Tiptop mines in Stanislaus County, and the Manganese Queen and J. M. McKnight Group in Trinity County. An extensive program by the Geological Survey and the Bureau of Mines was under way in 1942 to investigate and evaluate deposits of manganese-bearing ores in California. sults of these investigations have not yet been made available to the The Bureau of Mines 5 examined the Arlington Manganese Claims in Riverside County and recorded the findings in a war min-

Colorado.—The Pershing mine in Saguache County supplied the manganese ore shipped from Colorado during 1942. In addition, some ferruginous manganese ore was shipped from Gunnison County.

Georgia.—Georgia was the sixth-largest manganese ore-producing State in 1942. Of the total of 4,917 short tons shipped during the year, 4,715 tons came from the Cartersville district. This district

Johnston, T. L., Fine, M. M., and Shelton, S. M., Manganese Investigations—Metallurgical Division,
 11. Ore-Dressing Studies of Manganese Ores. Concentration of Manganese-Bearing Ore from the Bynum Property, Walnut Grove, Ala.: Bureau of Mines Rept. of Investigations 3637, 1942, 10 pp.
 4 Shelton, S. M., Fine, M. M., and Fisher, R. B., Manganese Investigations—Metallurgical Division.
 17. Ore-Dressing Studies of Manganese Ores. Concentration of Wad Ore from the Ayedalotte Property,
 Bureau of Mines, Arki: Bureau of Mines Rept. of Investigations 3652, 1942, 17 pp.
 Bureau of Mines, Arlington Manganese Claims, Riverside County, Calif.: War Minerals Report 92, 1943, 11 pp.

<sup>1943, 11</sup> pp.

The second secon

has shipped 205,600 short tons since operations began in 1866. The rest of the manganese ore shipped from Georgia in 1942 came from

Lincoln County.

A Bureau of Mines proposal to exhaust the Cartersville manganese reserves in about 2 years during the present emergency was rejected by the War Production Board because of equipment shortages.

Massachusetts.—Anson G. Betts shipped ferruginous manganese

ore from the Taconic mine in Hampshire County.

Michigan.—Ferruginous manganese ore totaling 34,643 short tons and averaging 13.11 percent (natural) manganese was shipped from

the Bengal mine in 1942.

Minnesota.—What is believed to be the first manganiferous ore from the Mesabi range was shipped during 1942; the Corsica mine yielded 33,880 short tons averaging 6.49 percent (natural) manganese, and the Alpena mine shipped 10,765 short tons averaging 6.31 percent (natural) manganese. The rest came from the Alstead-Hillcrest Group, Hopkins, Louise, Merritt, Mahnomen, and Sagamore mines in Crow Wing County.

Fine and others and Anderson have studied the beneficiation of

Missouri.—The output of manganese ore from Missouri came from

the Rocky Creek mine in Shannon County.

Montana.—Sixty-eight percent of the total metallurgical manganese ore and 77 percent of the high-grade battery ore shipped from mines in 1942 came from Montana. By far the largest operation in the State was the Manganese Reduction Works of the Anaconda Copper Mining Co. at Butte. In 1942 the ore was supplied by the Emma, Travona, and Anselmo mines. Battery-grade ore was shipped by the Moorlight Mining Co. and American Machine & Metals, Inc., from the Philipsburg district.

A Bureau of Mines proposal to erect a 400-ton custom mill at Butte, to treat manganese ores produced by several mines in that area, was approved by the Facility Review Committee of the War Production

Board in March 1943.

The mill is to be constructed by the Domestic Manganese Co., which applied for a \$250,000 loan from the Reconstruction Finance Corporation to finance the project. The Bureau of Mines in its exploratory work had drilled more than 10,000 feet of test holes, had taken many samples, and had tested the contemplated milling method. Known reserves of the four active mines in the area total about 175,000 tons of ore containing about 23 percent manganese. When milled and nodulized, the ore averages 51 to 59 percent manganese.

Under the contemplated program, the ore delivered to the mill will be purchased by the Metals Reserve Co., which has been buying ore for stock-piling in the Butte-Philipsburg region. The Domestic Manganese Co. proposes to mill and nodulize the stock-piled ore with the current production of the mines. When in full operation, the mill will produce about 2,000 tons of high-grade nodules per month. It is estimated that the milling plant can be constructed in about 90 days

<sup>&</sup>lt;sup>6</sup> Fine, M. M., Shelton, S. M., and Zadra, J. B., Manganese Investigations—Metallurgical Division. 9. Ore-Dressing Studies of Manganese Ores. Concentration of Manganiferous Iron Ore from the Armour No. 1 Mine, Ironton, Minn.: Bureau of Mines Rept. of Investigations 3624, 1942, 13 pp. <sup>7</sup> Anderson, C. Travis, and associates, Manganese Investigations—Metallurgical Division. 14. Hydrometallurgical Studies of Manganese Ores. Laboratory Experiments on Sulfur Dioxide-Sulfuric Acid Leaching of Black and Brown Manganiferous Ores of Cuyuna Range, Minn.: Bureau of Mines Rept. of Investigations 3649, 1942, 38 pp.

and that its rated capacity of 400 tons of crude ore a day will be ample to handle the output of mines now producing and to accommodate any new operations in the field.

Nevada.—Manganese ore and ferruginous manganese ore were shipped from the Black Diablo mine in Humboldt County in 1942. Relatively small shipments were made from the Black Rock mine in Lander County and the Last Hope mine in White Pine County.

The Manganese Ore Co., subsidiary of the M. A. Hanna Co. of Cleveland, is developing claims in the Las Vegas Wash, about 18 miles southeast of Las Vegas, Nev., which will be one of the largest domestic producers of high-grade manganese ore. Although the property is popularly described as the Three Kids mine and operations are actually in the same vicinity, there is no activity at the old Three Kids. About 100,000 tons of concentrates will be produced annually when full operations have begun, but it is believed that only about half that quantity will be shipped in 1943. As the analysis of the ore as mined is not consistent, a bedding system is necessary. About 250,000 tons of ore were mined in 1942, averaging 18.86 percent (natural) manganese.

New Mexico.—Shipments were made from Dona Ana, Grant, Luna, and Valencia Counties in 1942. The largest producing mine was the Luna in Luna County. The shipment statistics given for New Mexico in the tables do not include 6,508 tons (dry) of ore shipped to Deming for subasquent concentration.

for subsequent concentration.

Oklahoma.—A small quantity of ore averaging 42.4 percent manganese was shipped from the Lucky 13 mine in Coal County during 1942.

Oregon.—The output from Oregon in 1942 came from the McAdams property in Coos and Curry Counties and averaged 44 percent manganese.

Pennsylvania.—J. Harry Simon produced the manganese ore shipped from Pennsylvania in 1942 from Sherman Valley, Bedford County.

South Dakota.—The North Star Manganese Producers shipped manganese ore from the August Schedlin mine in Lawrence County during 1942.

Tennessee.—A considerable decrease in usable manganese ore shipments from Tennessee was apparent in 1942. Most of the ore came from the Embree mine in Unicoi County; however, shipments were also reported from Blount, Carter, Johnson, and Sevier Counties.

Texas.—Two small lots of ferruginous manganese ore were shipped

from Texas in 1942 for metallurgical purposes.

A study of the beneficiation of manganese-bearing ores from the Mayfield property at Van Horn has been made by Zadra and others.<sup>8</sup>

Utah.—Four shippers in Emery, Grand, and Juab Counties supplied the Utah total of 970 short tons of metallurgical ore and 78 short tons

of ferruginous manganese ore during 1942.

Virginia.—Virginia was second only to California in number of shippers in 1942. Nine concerns shipped metallurgical-grade ore, 11 shipped miscellaneous-grade, and 5 shipped ores of both grades; in addition, 5 concerns shipped ferruginous manganese ore during the year. Shipments of manganese ore were made from Augusta, Bath, Bland, Campbell, Craig, Roanoke, Smyth, and Washington Counties. Washington.—The Sunshine Mining Co. (second-largest shipper in

<sup>\*</sup>Zadra, J. B., Fine, M. M., Shelton, S. M., and Johnston, T. L., Manganese Investigations—Metalurgical Division. 13. Ore-Dressing Studies of Manganese Ores. Concentration of Manganese-Bearing Ore from the Mayfield Property, Van Horn, Tex.: Bureau of Mines Rept. of Investigations 3632, 1942, 18 pp.

人の下と おはいんなすんないのはない あしいまれている

the United States in 1942) shipped from the Crescent mine in Clallam County the State total of 10,660 short tons of metallurgical ore, averaging (dry) 52.12 percent manganese.

West Virginia.—The Appalachian Ores Co. shipped 2,240 short tons of metallurgical ore from the Sweet Springs mines in Monroe County.

## IMPORTS OF MANGANESE ORE

General imports of manganese ore containing 35 percent or more manganese decreased 15 percent from 1941 and comprised 7,963 short tons of battery ore and 1,316,361 short tons of other grades, chiefly for metallurgical use. In addition, 7,146 short tons of ferruginous manganese ore containing 2,086 short tons of manganese were imported during the year; of this quantity 4,413 tons containing 1,280 tons of manganese came from the Arabia Peninsular States, 2,240 tons containing 640 tons of manganese from Anglo-Egyptian Sudan, 490 tons containing 166 tons of manganese from Mexico, and 3 tons containing less than one-half ton of manganese came from Cuba. The bulk of the battery ore in 1942 came from Gold Coast (7,840 short tons containing 4,164 short tons of manganese); however, 67 short tons containing 36 short tons of manganese came from Canada, and 56 short tons containing 22 short tons of manganese came from Mexico.

Imports of manganese ore for consumption, which include ore with-drawn from bonded warehouses irrespective of date of entry, comprised 3,682 tons of battery ore containing 2,216 tons of manganese and valued at \$86,372 and 1,557,258 tons of other grades containing 764,183 tons of manganese and valued at \$22,922,524; in addition, 7,146 tons

of ferruginous manganese ore were imported.

The accompanying table shows the details of imports in 1941 and 1942 of ore of all grades except ferruginous manganese.

Manganese ore (35 percent or more Mn) imported into the United States, 1941-42, by countries

•		General in	norts 1	Imports for consumption 2						
Country		(short t				Shor	t tons		Ve	Jà
Coming	Gross	weight	Mnc	ontent	Gross weight Mn content		\ \ \*	Value		
	1941	1942	1941	1942	1941	1942	1941	1942	1941 ′	1942
Belgian Congo Brazil Chile Cuba Gold Coast India 3	433, 830 19, 191 272, 614 75, 823 360, 910	277, 410 1 149, 708 134, 194 493, 197	14, 181 183, 723 9, 046 129, 896 39, 636 181, 571	73, 098 68, 481 248, 695	353, 850 18, 305 272, 614 222, 776 433, 337	4, 462 149, 708 189, 236 585, 491	156, 711 8, 669 129, 896 113, 737 219, 756	2, 113 73, 098 95, 698 301, 777	\$3, 367, 812 366, 012 6, 353, 222 3, 224, 209 6, 270, 579	68, 542 3, 748, 261 2, 747, 845 8, 444, 228
Mexico Netherlands Indies Philippine Islands Union of South	4, 272 10, 363 63, 894	8, 059		4, 266	·	9, 067	l	4, 758	26, 962 250, 463 1, 000, 460	203, 875
Africa	292, 739  136		136, 936  72		32, 685		16, 929		393, 370	277, 216
	1, 562, 133	1, 324, 324	733, 275	631, 913	1, 714, 581	1, 560, 940	824, 956	766, 399	25, 085, 831	23, 008, 896

<sup>1</sup> Comprises ore received in the United States during year; part went into consumption, and remainder

entered bonded warehouses.

Comprises receipts during year for consumption and ore withdrawn from bonded warehouses during year (irrespective of time of importation).

India and Dependencies (British India).

#### STOCKS OF MANGANIFEROUS RAW CONSUMPTION AND MATERIALS

The total consumption of manganese ore in 1942 increased 13 percent over 1941 and amounted to 1,481,672 short tons; of this total, 1,435,388 tons or 97 percent was of foreign origin. Industrial stocks of manganese ore on December 31 were 26 percent less in 1942 than

The accompanying table shows actual consumption of manganese ore (containing 35 percent or more manganese, natural) and alloys

during 1942 and stocks at the end of the year.

Manganese ore and manganese alloys consumed and in stock 1 in the United States in 1942, gross weight in short tons

프라마셔트 불통하다 보면 얼마나 나는 그 중요한다.	的物设备计	In stock De	c. 31, 1942 <sup>1</sup>
	Consumed	At plant (in- cluding bonded warehouses)	In bonded warehouses
Manufacturers of manganese alloys: Manganese ore: Domestic: 35 to 47 percent Mn (natural)	24, 407	8, 495	
Over 47 percent Mn (natural)  Foreign	2, 576 1, 384, 255	5, 875 818, 870	423, 866
Ferromanganese Spiegeleisen Silicomanganese Manganese briquets	1, 411, 238	833, 240 64, 276 9, 581 746 621	423, 86 52, 84
Manufacturers of iron and steel:  Manufacturers of iron and steel:  Manganese ore: Domestic: 35 to 47 percent Mn (natural) Over 47 percent Mn (natural) Foreign	4, 422 2, 566 22, 884	2, 120 707 7, 220	
Ferromanganese Spiegeleisen Silicomanganese Manganese briquets	29, 872 665, 299 181, 052 46, 694 3, 482	10, 047 145, 433 78, 651 4, 547 879	
Manufacturers of dry cells: Manganese ore: Domestic: 35 to 47 percent Mn (natural)	3,099	6, 975	
Over 47 percent Mn (natural)	9, 157 24, 246	2, 406 19, 272	11, 21
Manufacturers of chemicals: <sup>2</sup> Manganese ore: Domestic: 35 to 47 percent Mn (natural) Over 47 percent Mn (natural) Foreign	27 30 4,003	28, 653 315 1, 556 11, 424	11, 21
	4,060	13, 295	
Brokers and dealers:  Manganese ore: Domestic: 35 to 47 percent Mn (natural) Over 47 percent Mn (natural) Foreign		317	
Ferromanganese		509	
Grand total:  Manganese ore: <sup>2</sup> Domestic: 35 to 47 percent Mn (natural) Over 47 percent Mn (natural) Foreign.	14, 329 1, 435, 388	857, 103	435, 0
Ferromanganese	46, 694	210, 047 88, 232 5, 293	435, 08 52, 84

<sup>1</sup> Excluding Government stocks.
2 Data for manufacturers of chemicals cover 4 months, September to December, only.

The accompanying table shows ores available for consumption in the United States in 1942 but does not consider consumer or Government stocks at the beginning and end of the year.

Indicated consumption of manganiferous raw materials in the United States in 1942

		aining 35 t or more	contair	residuum ning 10 to ent Mn	Ore containing 5 to 10 percent Mn		
	Short tons	Mn content (percent)	Short tons	Mn content (percent)	Short tons	Mn content (percent)	
Domestic shipments Imports for consumption	190, 748 1, 560, 940	53. 3 49. 1	560, 815 7, 146	14. 9 29. 2	1, 500, 613 1 1, 780	8. 0 6. 2	
Total available for consumption	1, 751, 688	49. 6	567, 961	15. 1	1, 502, 393	8.0	

<sup>1</sup> Estimated.

## METALLURGICAL INDUSTRY

The bulk of the manganese ore (95 percent in 1942) used in the United States is for the manufacture of manganese alloys, and virtually all alloys are consumed by the iron and steel industry. During 1942 steel producers consumed 12.4 pounds of metallic manganese per ton of steel produced; of this, 11.2 pounds was in the form of ferromanganese, 0.6 pound as spiegeleisen, and 0.6 pound as silicomanganese. Ferromanganese producers used an average of 1.952 short tons of manganese ore per ton of ferromanganese produced.

Ferromanganese.—The domestic output of ferromanganese in 1942, which increased 14 percent over 1941, was produced at the following

plants:

Bethlehem Steel Co., Johnstown, Pa.
Colorado Fuel & Iron Corporation, Pueblo, Colo.
E. J. Lavino & Co., Reusens, Va., and Sheridan, Pa.
Sloss-Sheffield Steel & Iron Co., North Birmingham, Ala.
Tennessee Coal, Iron & Railroad Co., Holt, Ala.
Carnegie-Illinois Steel Corporation, Etna and Clairton, Pa., and Gary, Ind.
Electro-Metallurgical Co., Alloy, W. Va., and Niagara Falls, N. Y.
Tennessee Products Corporation, Rockdale and Rockwood, Tenn.

In addition to the foregoing plants, shipments were made by the Keokuk Electro-Metals Co., Keokuk, Iowa.

Most of the ferromanganese produced in this country is made from foreign ores, as shown in the accompanying table.

Ferromanganese and spiegeleisen imported into and made from domestic and imported ores in the United States, 1941-42, in short tons

등으로 하다면 하다는 그리고 중요하다	194	·	1942	2
	Alloy	Manga- nese	Alloy	Manga- nese
Ferromanganese:	7, 032	5, 696	14, 772	11, 617
	580, 704	461, 539	661, 338	522, 553
Domestic production	21, 926	17, 795	12, 335	10, 514
From domestic ore 1	558, 778	443, 744	649, 003	512, 039
From imported ore 1	EOT 700	467, 235	676, 110	534, 170
Total	587, 736	407, 200	070, 110	004, 110
Ratio (percent) of Mn in ferromanganese of domestic or-	1111	3, 81		1.97
igin to total Mn in ferromanganese made and imported		5, 51	13	1.9
Number of plants making ferromanganese	12		13	
			- 000	1 000
Spiegeleisen: Imported	4, 741	1 949	1,990	1 398
Domestic production	177, 915	28, 679	186, 026	36, 071
From domestic oreFrom imported ore	175, 543	28, 297	186, 026	36, 07
From imported ore	2, 372	382		
Motel .	182,606	29, 628	188, 016	36, 46
Potic (percent) of Mn in spiegeleisen of domestic origin to				
total Mn in spiegeleisen made and imported	1	95. 51		98.9
Number of plants making spiegeleisen	1 5		4	
Total available supply of metallic manganese in ferro-				
mongonese and spingeleisen	1	496, 863		570, 63
Downer of available supply of manganese in-	3			
Townsmanganasa and smissellisen immoried		1.34		2.1
Ferromanganese made from imported ore		89. 31		89.7
Griegologen made from imported ore		. 08		
Spiegeleisen made from imported ore Ferromanganese made from domestie ore		3.58		1.8
Spiegeleisen made from domestic ore		5.69		6.3
Ferromanganese and spiegeleisen made from domestic ore.				8.1
refromanganese and spiegereisen made nom domestic ore.		5. 96		6.3
Spiegeleisen made and imported	82 836 048	0.00	86, 029, 921	0.0
Total open-nearth, Bessemer, and electric steel	02,000,940		00, 020, 021	

<sup>1</sup> Estimated.

# Ferromanganese produced in the United States and metalliferous materials consumed in its manufacture, 1938-42

	Ferroma	anganese pi	roduced	Mater	Manga-			
Year	Short	Manganese con- tained		Manganese ore (35 percent or more Mn, natural)		Iron and manga- niferous	Cinder, scale, and pur-	nese ore used per ton of ferroman- ganese made
	tons	Percent	Short tons	Foreign	Do- mestic	iron ores	chased scrap	(short tons)
1938 1939 1940 1941 1942	272, 153 302, 524 514, 682 580, 704 661, 338	78. 65 79. 24 79. 45 79. 48 79. 01	214, 036 239, 725 408, 903 461, 539 522, 553	466, 746 563, 344 976, 332 1, 122, 187 1, 273, 596	25, 254 13, 419 9, 414 17, 572	10, 860 9, 323 5, 889 5, 166 19, 545	9, 477 7, 000 1 8, 868 6, 031 4, 634	1. 808 1. 862 1. 923 1. 949 1. 952

<sup>&</sup>lt;sup>1</sup> Corrected figures.

Manganese ore used in manufacture of ferromanganese in the United States, 1938-42, by sources of ore

	19	1938		1939		1940		1941		1942	
Source of ore	Gross weight (short tons)	Mn con- tent (per- cent)									
DomesticForeign:	25, 254	53. 20			13, 419	55. 89	9, 414	41. 61	17, 572	39. 69	
Africa Brazil	171, 022 71, 747	48. 99 41. 44	144, 734 65, 278		233, 370 189, 389	45. 89 42. 39		47. 11 42. 29		46. 6 41. 5	
Chile Cuba	40, 650	48. 07	959	48. 16	6,076	46. 13	4,715	45.81	5, 677	46.6	
IndiaJava	62, 681	49. 24			112, 859 188, 079	48. 59 49. 73		48. 47 49. 85	340, 096	49.7	
Mexico Philippine I slands					12, 768	47. 16	1,755 6,2 <b>3</b> 6	46. 27 48. 32	2, 189 2, 013	46. 2 45. 3	
U. S. S. R. Undistributed	120, 646	47. 61	189, 628	47. 54	187, 286 46, 505	47. 85 38. 75	1 145, 325	48. 12 46. 26		46. 0 48. 0 45. 7	
	492, 000	47. 72	563, 344	47. 72	989, 751		1, 131, 601		1, 291, 168		

<sup>&</sup>lt;sup>1</sup> Tonnage entered under "Undistributed" comprises ore from India and U. S. S. R.; separation as to source not reported by consumer.

<sup>2</sup> Source of ore not reported by consumer.

Shipments of ferromanganese in 1942 increased 6 percent over 1941. The record of shipments for the past 5 years is as follows:

Ferromanganese shipped from furnaces in the United States, 1938-42

Year	Short tons	Value	Year	Short tons	Value
1938	250, 566 332, 227 503, 291	\$19, 144, 884 24, 137, 211 42, 755, 485	1941 1942	619, 395 659, 219	\$69, 378, 004 82, 726, 298

Imports for consumption and exports increased 110 and 39 percent, respectively, over 1941. Ferromanganese imported in 1942 totaled 14,772 short tons, all containing not less than 4 percent carbon.

Ferromanganese imported into and exported from the United States, 1938-42

	Impor	ts for consur	Exports 1		
Year	Gross weight (short tons)	Mn content (short tons)	Value	Gross weight (short tons)	Value
1938 1939 1940 1941 1942	29, 409 46, 175 11, 613 7, 032 14, 772	23, 652 37, 424 9, 601 5, 696 11, 617	\$1, 770, 948 2, 935, 214 1, 321, 369 557, 150 1, 274, 749	277 3, 274 14, 600 5, 155 7, 165	\$18, 799 247, 798 1, 366, 087 771, 575 976, 923

<sup>&</sup>lt;sup>1</sup> 1938-41: Includes spiegeleisen; not separately classified prior to July 1, 1941.

Imports of ferromanganese in 1941 and 1942, by countries, are shown in the following table.

Ferromanganese imported for consumption in the United States, 1941-42, by countries

	19	11	1942		
Country	Mn content (short tons)	Value	Mn content (short tons)	Value	
CanadaNorway	1, 202 13	\$136, 029 1, 597	5, 022 6, 595	\$654, 219 620, 530	
United Kingdom 1	4, 481 5, 696	419, 524 557, 150	11, 617	1, 274, 749	

<sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

The quoted price per short ton of ferromanganese was increased from \$111.90 to \$125.58 May 1, 1942, in compliance with Office of Price Administration Price Regulation 138. No further change was in prospect at the close of 1942.

Prices per short ton of ferromanganese in the United States, 1940-42, by months 1

Month	1940	1941	1942	Month	1940	1941	1942
January	\$94. 04	\$111. 90	\$111. 90	July	\$111. 90	\$111. 90	\$125. 58
February	94. 04	111. 90	111. 90		111. 90	111. 90	125. 58
March	94. 04	111. 90	111. 90		111. 90	111. 90	125. 58
April	94. 04	111. 90	111. 90		111. 90	111. 90	125. 58
May	94. 04	111. 90	125. 58		111. 90	111. 90	125. 58
June	94. 04	111. 90	125. 58		111. 90	111. 90	125. 58

<sup>1</sup> Steel, vol. 112, January 4, 1943.

Spiegeleisen.—Domestic production of spiegeleisen in 1942 increased 5 percent over 1941 and 63 percent over 1940.

Spiegeleisen produced and shipped in the United States, 1938-42

	Produced		ed from naces		Produced		ed from aces
Year		Short tons	Value	Year	(short tons)	Short tons	Value
1938 1939 1940	12, 668 102, 470 114, 119	27, 932 94, 908 119, 512	\$728, 830 2, 484, 042 3, 487, 565	1941 1942	177, 915 186, 026	181, 177 186, 163	\$5, 793, 481 5, 931, 728

Spiegeleisen was manufactured at the following plants during 1942: Carnegie-Illinois Steel Corporation, Clairton and Duquesne, Pa., and South Chicago, Ill. New Jersey Zinc Co., Palmerton, Pa.

All the spiegeleisen produced in the United States in 1942 was made from domestic raw materials. Imports of spiegeleisen for consumption decreased 58 percent from 1941; the total supply came from Canada.

		United States,	

	Year	Shorttons	Value	Year	Shorttons	Value
1938 1939 1940		19, 318 42, 856 17, 455	\$625, 480 1, 329, 814 638, 732	1941. 1942.	4, 741 1, 990	\$215, 108 95, 853

The prices of spiegeleisen (20 percent) at producers' furnaces as quoted by Steel were constant at \$32.14 a short ton throughout 1942.

Manganiferous pig iron.—Precise data on consumption of manganiferous ores in the production of manganiferous pig iron are not available. However, 1,500,613 short tons of domestic ore containing 5 to 10 percent manganese and 557,498 short tons containing 2 to 5 percent manganese were shipped during 1942. A small quantity (1,780 short tons) of foreign manganiferous iron ore and 13,950 short tons of foreign ferruginous manganese ore were also consumed in the manufacture of pig iron.

Foreign ferruginous manganese ore and manganiferous iron ore consumed in the United States, 1940-42, in short tons

Source of ore		Ferruginous manganese ore			Manganiferous iron ore			
	Boards of ore		1940	1941	1942	1940	1941	1942
Africa			206 40, 397					
Asia: Palestin Australia Brazil	ө 		40, 397	8,313	9,173	13, 334	2, 265	790
Cuba Sweden			600	0,010	4,777	586		990
			41, 439	8, 313	13, 950	13, 920	2, 265	1, 780

# BATTERY INDUSTRY

Shipments of battery ore containing over 35 percent manganese amounted to 12,377 short tons in 1942, and shipments of ore containing less than 35 percent manganese for battery manufacture totaled 3,033 short tons. It is believed that 1942 was the first year in which ferruginous manganese ore was purchased for this purpose. During 1942 the battery industry consumed 12,256 short tons of domestic ore and 24,246 short tons of foreign ore compared with 11,642 and 26,342 short tons, respectively, in 1941.

Manganese ore for battery use should have a high content of available oxygen with minimum iron and be relatively free from such metals as arsenic, copper, nickel, or cobalt, which are electro-

negative to zinc.

#### MISCELLANEOUS INDUSTRIES

During the last 4 months of 1942, 4,060 short tons of manganese ore were consumed in the chemical industries. Virtually all the chemical ore used in this country is of foreign origin; of the total consumed in 1942, only 57 short tons were of domestic origin. Chemical-grade ore has a great many uses, but most of it is used for photography, fertilizers, and coloring agents in paints and ceramics.

#### PRICES

Prices of manganese ore (except battery ore) are upon a unit basis, the unit being 1 percent of a long ton (22.4 pounds) of contained manganese. Prices of battery-grade ore are quoted upon a per-ton

basis, with a minimum requirement of manganese dioxide.

Ferromanganese.—Standard ferromanganese containing 75 to 85 percent manganese was placed under formal price regulations on May 1, 1942. A price of \$135.00 per long ton (\$120.50 per short ton) f. o. b. Atlantic Seaboard, except for two Southern producers for whom the price is established on an f. o. b. furnace basis, was made effective in this order. This price represented an increase of \$15.00 per long ton over the price which had prevailed since October 1-15, Other than manganese, standard ferromanganese was defined as metal containing a maximum of 1.25 percent silicon, 0.50 percent phosphorus, 7.50 percent carbon, and 0.05 percent sulfur. The maximum prices by grades were established as follows:

Kind or grade:

Maximum price per long ton

Containing 78-82 percent manganese\_\_\_\_ Containing less than 78 percent manganese but not less than 75 percent.

Containing more than 82 percent manganese but not more than 85 percent.

\$135.00. \$135.00 less \$1.70 for each 1 percent of manganese below 78 percent. \$135.00 plus \$1.70 for each 1 percent of manganese in excess of 82 percent.

Manganese ore.-Maximum Price Regulation 248 was released October 27, 1942 (effective November 9, 1942), fixing the price of all manganese ore except battery and chemical ore at the following long-ton unit rates:

85 cents f. o. b. railroad cars Mobile and New Orleans.

90 cents f. o. b. railroad cars Norfolk, Baltimore, Philadelphia, and New York. 96 cents f. o. b. railroad cars Fontana, Calif.; Pueblo, Colo.; and Provo, Utah.

These prices are for metallurgical ore of a base analysis of manganese 48 percent, iron 6 percent, silica plus alumina 11 percent, and phosphorus not over 0.18 percent upon a dry basis. Premiums and penalties due to variation of analysis are as follows:

#### Premiums

Manganese content above 48 percent: ½ cent for each 1 percent. Iron content below 6 percent: ½ cent for each 1 percent. Silica plus alumina content below 11 percent: Nothing. Phosphorus below 0.18 percent: Nothing.

#### Penalties

Manganese content:

Below 48 percent: 1 cent for each 1 percent down to and including 44 percent. Below 44 percent: 4 cents, plus 1½ cents for each 1 percent down to and including 40 percent.

Below 40 percent: 10 cents, plus 2 cents for each 1 percent down to and including 35 percent.

Above 6 percent: 1 cent for each 1 percent up to and including 8 percent. Above 8 percent: 2 cents, plus ¾ cent for each 1 percent.

Silica plus alumina content:
Above 11 percent: 1 cent for each 1 percent up to and including 15 percent Above 15 percent: 4 cents plus 3/4 cent for each 1 percent. Phosphorus content:

Above 0.18 percent: 1/2 cent for each 0.01 percent.

The above premiums and penalties are applied pro rata to variations of a fraction of 1 percent.

Amendment 1 to Price Regulation 248 was issued November 30, 1942 (effective December 1, 1942), exempting metallurgical manganese ore with a manganese content of 40 percent or less. Previously ore

of 35 percent or less manganese content was exempt.

The average mine value reported for ore containing 35 percent or more manganese during 1942 was about 72 cents per long-ton unit. Quotations on imported ore in the following table are from Engineering and Mining Journal. A duty of one-half cent per pound of contained manganese is imposed on all imported manganese ore except that from Cuba and Philippine Islands, which enters duty free.

Domestic prices of imported metallurgical manganese ore in 1942, in cents per longton unit

	Begin- ning of year	End of year		Begin- ning of year	End of year
Brazilian, 46–48 percent Mn Chilean, 47–48 percent Mn South African, 50–52 percent Mn	\$0.630 .650 (1)	\$0.788 .788	Cuban (not dutiable): 50-52 percent Mn45-47 percent Mn	\$0. 780 (¹)	\$0. 915 . 900

[C. inf. North Atlantic ports, cargo lots, exclusive of duty]

According to Engineering and Mining Journal, prices for chemical ores per long ton in carlots at the end of 1942 were as follows: Domestic, containing 70 to 72 percent MnO<sub>2</sub>, \$45 to \$50; Brazilian or Cuban, 80 percent, \$55; Javan or Caucasian, 85 percent, \$70 to \$75.

#### WORLD PRODUCTION

Brazil.—The bulk of the manganese ore from Brazil comes from the Morro da Mina mine in the Lafayette district in Minas Geraís and the Urucum mine in Matto Grosso. During 1942, a total of 277,410 short tons was imported into the United States from Brazil, compared with 433,830 short tons in 1941. Brazil was our second-largest supplier in 1942.

Chile.—Production in Chile amounted to 32,692 short tons of 46- to 49-percent ore in 1942. Virtually none reached the United

States during the year.

Cuba.—The Cuban American Managanese Corporation produced 198,286 long dry tons at the Isabelita mine in Oriente Province and shipped 159,686 long tons from Santiago and Antilla during the year. Stocks of ore at the mine and mill totaled 51,565 long tons at the close of the year.

French Morocco.—During the first 6 months of 1942, exports totaled

15,762 short tons.

Gold Coast.—Production in Gold Coast totaled 488,322 short tons in 1940 and 549,922 short tons in 1941. Stocks on hand October 31, 1942, at ports were 78,000 short tons and at mines 170,000 short tons.

India and Dependencies.—India was probably the world's largest producer of manganese ore in 1942—about 1,000,000 tons of ore is produced annually. During 1942 the United States received 493,197 short tons of ore from that country.

Turkey.—The production of manganese ore from Turkey comes from the Afyon and Eskisehir regions. During 1941 the output totaled

<sup>1</sup> Not quoted.

1.499 short tons and during the first 6 months of 1942, 569 short

tons. The ore averaged 47 to 48 percent manganese.

Union of South Africa.—Data for only the first 11 months of 1941 and 1942 are available. During these respective periods, 460,161 and

404,462 short tons were produced.

U. S. S. R.—The Soviet Union continued to be a leading nation in manganese-ore production, but because of enemy occupation production dropped considerably in 1942—probably to less than 1,000,000 tons.

Manganese ore produced in principal countries of the world, 1938-42, in metric tons 1 [Compiled by B. B. Waldbauer]

Country 1	Percent Mn	1938	1939	1940	1941	1942
North America:		V. 1 1 1 19		•		
Canada (shipments)		la guardia	359	138	(2)	63
Costa Rica		304	(3)	(2)	(2)	(2)
Cuba	36-50-	123, 844	102, 415	119,852	191, 937	201, 46
Mexico	40+	120,041	27	307	979	11, 49
	30 1	111		501	1	11, 10
United States:	35+	25, 727	29, 777	40, 767	79, 646	173, 04
Continental (shipments)			20,111	40, 101	10,040	170,09
Puerto Rico (exports)	48-51	1,039				
South America:	07.00	407	0.51	770	1 450	(0)
Argentina 4 Bolivia (exports)	35-38	437	651	710	1,476	(2)
Bolivia (exports)	50		500		(2)	27
Brazil	3850	306, 025	257, 752	313, 391	5 437, 402	5 306, 24
Chile	40-50	19, 319	12, 550	11,620	35, 815	29, 65
Peru		24	96	283	(2)	(2)
Europe:						
Bulgaria	30-45	1,887	944	2,000	(2)	(2)
Germany	30+	163	(3)	(2)	(2)	(2) (2)
Greece	30-	7,075	11, 178	(2)	(2)	(2)
Hungary.	35-48	22, 221	(3)	(2) (2) (2) (2)	(2) (2) (2) (2) (2)	(2)
nungary	34-37	48, 282	54, 100	2	2	()
Italy			353	1,059	1,815	6, 82
Portugal	40+	1,008			(2)	
Rumania	30-36	60, 256	41,546	(2)		(2)
Spain		1, 319	4,711	5, 865	9, 923	19,69
Sweden	30-50	5, 347	5, 934	(2)	(2)	(2)
U. S. S. R	41-48	2, 272, 800	(3)	2, 800, 000	6 3, 000, 000	(2)
Yugoslavia	32-38	3, 759	5, 655	(2)	7 4, 724	(2)
Asia:					1 1	
China (exports)	45-46	1, 247	. 1	(2)	(2)	(2)
India:	20 20		· -		1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	1
British	47-52	983, 464	858, 220	(2)	61,000,000	(2)
Portuguese	42-50+	9, 478	8, 204	6, 525		25
Indochina	12 00 1	2, 214	2, 440	6 2, 000	(2)	(2) (2) (2) (2)
	49-51	6 80, 000	(3)	(2)	(2)	(2)
Japan			12,074	11, 569	(2)	(2)
Netherlands Indies	50-55	9,687			900 004	(2)
Philippine Islands	45-50	58, 143	29, 394	52, 166	8 33, 664	
Turkey	30-50	2, 186	3, 339	460	1, 360	61,00
Unfederated Malay States	30	32, 483	31, 952	11,702	(2)	(2)
Africa:		1				
Belgian Congo	56	7, 725	(3)	18, 369	(2) 2, 175	6 36, 00
Egypt	30+	153, 112	119,882	64, 912	2,175	6 9, 00
Gold Coast	50+	408, 452	388, 131	442, 998	498, 881	(2)
Morocco:	1		1		1	
French	40-50+	86, 597	50, 803	(2)	(2)	8 14, 29
Spanish	38	152	(3)	(2)	(2)	(2)
Northern Rhodesia	30-48	2,779	3, 018	(2)	2	(2)
Union of South Africa	30-51	551, 739	419, 697	412, 071	9 417, 451	9 366, 92
	30-01	OOT, 199	310,001	112,011	211, 201	, ,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,
Oceania:			l .	1		1
Australia:	1 -	004	140	1 004	1 40#	(2)
New South Wales		221	148	1,024	1, 485	(2) (2) (2) (2)
Queensland		382	\	387	209	1 . 12
South Australia			7	10, 827	11, 406	) (2)
New Zealand		91	494	996	764	(2)
Papua			55	198	408	(2)
	1	5, 291, 000	5, 169, 000	(2)	(2)	(2)

<sup>&</sup>lt;sup>1</sup> In addition to countries listed, Belgium produces manganese ore, but data of output are not available. Czechoslovakia reports a production of manganese ore, but as it has been ascertained that the product so reported averages less than 30 percent Mn and therefore would be considered ferruginous manganese ore under the classification used in this report, the output has not been included in the table.

Data not available.
 Estimate included in total.

Shipments by rail and river.

Exports.

6 Estimated.

7 Croatia only.

8 Exports January to June, inclusive. 9 January to November, inclusive.

# **CHROMITE**

By FREDERICK BETZ, JR.

#### SUMMARY OUTLINE

	Page		Page
Summary	631	United States—Continued	- : <del>-</del> :
Salient statistics	631	Historic data	634
War regulations	632	Exploration and development	637
Market and prices	632	Uses and consumption	638
United States	634	Imports and exports	639
Production in 1942	634	World production	640

#### SUMMARY

The substantial increase in domestic chromite shipments to an all-time record of 112,876 short tons was an outstanding feature of the chromite industry in 1942—an achievement made possible through the opening of the Montana deposits, from which no commercial production had previously been realized. This large output represents the fruition of efforts by Government agencies to free the United States from complete dependence on foreign sources for its chromite It must be remarked, however, that the quality of domestic chromite tends to offset in part the volume of shipments, as much of the product was unsuitable for metallurgical use. Concomitantly with the stimulation of domestic production, the Government has continued to develop its stock-piling program, whereby adequate supplies of foreign chromite are being procured to fulfill wartime requirements. The Government also undertook to correlate supply with requirements by placing chromium under complete allocation in 1942.

Salient statistics of chromite (ores and concentrates) in the United States, 1940-42

	1940	1941	1942
Shipments from domestic mines—			
By grades:  45 percent Cr <sub>2</sub> O <sub>3</sub> minimumshort tons_ 35 to 45 percent Cr <sub>2</sub> O <sub>3</sub> do  Less than 35 percent Cr <sub>2</sub> O <sub>3</sub> do	267	4, 800	18, 986
	2, 400	9, 208	76, 108
	315	251	17, 782
Total: Short tonsValue	2, 982	14, 259	112, 876
	\$28, 784	\$274, 062	\$2, 994, 081
Imports for consumption: Short tons. Value	736, 612	1, 115, 292	980, 487
	\$8, 754, 770	\$12, 618, 581	\$14, 184, 159
Exports: Short tons	(1)	<sup>2</sup> 1, 906	4, 743
	(1)	<sup>2</sup> \$72, 409	\$163, 420

<sup>1</sup> Data not available.

Figures cover July to December; not separately classified before July.

The U. S. S. R. is assumed to be the world's leading chromite producer. Next in order of importance are Southern Rhodesia, Union of South Africa, and Cuba. Thus the United Nations command the chief sources of supply. The Axis Nations control the output of continental Europe, which includes, as relatively important producers, Yugoslavia and Greece; they have also acquired the resources of the Philippine Islands, which in recent years had developed a significant production. With the little information at hand, it seems safe to estimate the Axis supply at not more than one-fourth the total world output. In the struggle to obtain larger supplies of chromite, Germany has made strenuous efforts to obtain the production of Turkey by trade negotiation. It is still doubtful whether this has actually been accomplished.

WARTREGULATIONS

Delivery of ferrochromium, other chromium alloys, and chromium metal was placed under Government control by the Office of Production Management in November 1941. The use of ferrochromium was limited to 2 tons per month without specific authorization in January 1942. The War Production Board extended allocation in February by requiring an application for all consumption of metallurgical chromium products.

The quantity of chromite that can be used in the manufacture of chromium chemicals has been restricted since November 1941, and the consumption of chromium chemicals has been controlled since

March 1942.

A more detailed discussion of Government regulations appears in the chapter on Chromite in Minerals Yearbook, 1941.

#### MARKET AND PRICES

The Metals Reserve Co. has become the principal purchaser of domestic chromite since its buying program was announced in November 1941. Originally this Government agency undertook to contract for lots of 5,000 to 10,000 long tons of ore produced in continental United States, but in December 1941 the minimum size of contracts was lowered to 1,000 tons. In March 1942 the program was extended to include the purchase of trucklots of chromite produced in Oregon and northern California at nearby depots, with the object of encouraging production from small deposits in this region and providing an easily accessible market. Deliveries of ore to purchase depots in small lots did not constitute fulfillment of contracts. As defined in June 1942, small lots consisted of not less than 10 tons, the minimum quantity for which payment was to be made upon delivery. On September 10 the terminating date of the small-lot purchasing program was moved from April 1, 1943, to December 31, 1943.

The purchasing schedules have undergone several revisions with respect to type of material acceptable, grade and size of ore, and prices. Three grades, specifications for which are summarized in the accompanying table, were listed in 1942 schedules. The original minimum for Low-Grade A and B ore was 40 percent Cr<sub>2</sub>O<sub>3</sub>, but in the May 1942 revision of the schedule a minimum of 35 percent in these grades

became acceptable.

The grades and prices (f. o. b. stock pile designated by buyer) established by Metals Reserve Co. follow:

기가 있는 사람이 하는 사람이 되었다.	High-	Low-Grade	
	Grade	A	В
Grade specifications:   Cr2Os	45.00 11.00 .20 .50 2.5:1 \$40.50 .90 1.50	40.00 13.00 .50 1.00 2.0:1 \$28.00 .90 1.50	40. 00 None None None S24. 00

Imported ores were given nominal quotations in E&MJ Metal and Mineral Markets during the first 10 months of 1942. Metallurgicalgrade Indian and African ore (48 percent Cr<sub>2</sub>O<sub>3</sub>, Cr:Fe=2.8:1) was quoted at \$39 per long ton, c. i. f. Atlantic ports, and Brazilian ore (48 percent, Cr:Fe=3:1) was priced at \$41.

On November 3, 1942, the Office of Price Administration issued Maximum Price Regulation 258 for chromite ores. As explained in the memorandum accompanying the order, the ceilings are approximately at the levels prevailing during the first 6 months of 1942 for metallurgical and chemical ores and between the first half of 1942 and early November prices for refractory ores. The regulation, which became effective November 9, does not apply to sales of chrome ore to the Government or to sales where the contract of sale is made and title vests in the buyer while the ore is outside the continental United States. However, sales by Government agencies to private purchasers are included in the regulation. As a result, the Metals Reserve Co. may establish any price to stimulate domestic production and assure importation of adequate supplies of foreign ore. The maximum base prices are fixed f. o. b. railroad cars at various favorable basing points for industrial users (for example, New York, Philadelphia, Baltimore).

Maximum prices of chromite established by Office of Price Administration, effective November 9, 1942

Metallurgical-chemical ores: Analysis: Base—48 percent Cr <sub>2</sub> O <sub>3</sub> and Cr: Fe=3.0:1; minimum	-25 percent Cr <sub>2</sub> O <sub>8</sub> .	
Prices:	-	
Base	per long ton	1 3 \$43.50
Premiums for—		
Increase in Cr2O3 above 48 percent	per long-ton unit	.90
Increase in Cr: Fe to 3.5:1		1. 25
Penalties for —	por toman	1.20
Decrease in Cr2Os to 25 percent	per long-ton unit	.90
Decrease in Cr: Fe to 2.0:1	per tong-ton unit	1. 25
Refractory ores:	per tenen	1, 20
Analysis: Minimum—25 percent Cr2Os.		
Base prices:		
Lump ore (in bulk)		
	per long ton	31.00
Ground ore, 24-mesh or coarser (in bulk)	per short ton	~ 36.50

For Montana ores and concentrates only, base price is f. o. b. railroad cars at Columbus, Mont., with allowance to buyer for actual freight not in excess of \$7.00 per long ton.
 Increase of \$3.50 per long ton is allowed for sales and deliveries in lots of 1 carload or less.
 Quantity and packing differentials are provided; see Maximum Price Regulation 258 for details.

The Office of Price Administration also ordered that a maximum export premium of \$6 per long ton might be charged on an export 556250-43sale of domestic chrome ore and concentrates containing 38 to 44 percent Cr<sub>2</sub>O<sub>3</sub> as of November 9.

# UNITED STATES

# PRODUCTION IN 1942

The domestic production of chromite in terms of shipments from mines reached the unprecedented total of 112,876 short tons in 1942 or almost 8 times as much as in 1941. The previous record of 92,322 tons was made in 1918. In establishing the new record, Montana contributed over half the total. This is all the more remarkable as no shipments of chromite have ever been reported from Montana before. California produced 40 percent of the total, and the remainder was shipped from deposits in Oregon, Idaho, and Washington.

The average grade of chromite (ore and concentrates) shipped in 1942 was 39 percent  $Cr_2O_3$ . The highest average grade was produced in California (44 percent  $Cr_2O_3$ ). Although Montana was the leading producer, the product was lowest in grade, averaging only 36 percent  $Cr_2O_3$ . Of the total shipments, 17 percent contained a minimum of 45 percent  $Cr_2O_3$ , 67 percent ranged in  $Cr_2O_3$  content from 35 to 45 percent, and 16 percent contained less than 35 percent  $Cr_2O_3$ .

There were 150 shippers, and almost three-quarters of them operated in California. Two shippers in Montana and 11 in California supplied 90 percent of the total. Less than 30 percent of the shippers, all with production of over 100 tons, contributed 97 percent of the total.

Chromite (ore and concentrates) shipped from mines in the United States, 1900-1942

Period	California	Maryland and North Carolina	Oregon	Other States <sup>1</sup>	Total	Total value
1900-1904 1905-1909 1910-1914 1915 1916 1917 1918 1919 1920-1924 1925-1929 1930-1934 1935-1939 1940	1, 228 1, 119 1, 442 3, 675 49, 009 41, 187 70, 725 3, 664 2, 194 1, 451 1, 921 1, 921 1, 419 2, 713 13, 419 44, 873	95 100 210 533 77 217 93	3, 471 7, 506 20, 669 603 1, 535 269 840 2, 683	423 100 70 395 1, 344 147 	1, 228 1, 542 1, 537 3, 675 52, 680 48, 973 92, 322 5, 688 4, 093 1, 544 1, 921 1, 8, 435 2, 982 14, 259 112, 876	\$15, 852 23, 345 18, 680 36, 744 726, 243 1, 049, 685 129, 302 60, 004 28, 033 23, 812 81, 651 28, 74, 066 2, 994, 081

<sup>1</sup> Idaho, Montana, Washington, and Wyoming.

California.—The new Grey Eagle mill of the Rustless Mining Corporation in Glenn County was the largest chromite producer in California in 1942. Production began in February and during the year totaled 11,153 tons of concentrates, averaging 46 percent Cr<sub>2</sub>O<sub>3</sub> and 11 percent Fe. A roughly tabular mass about 800 feet long and 4 to 50 feet thick is now being mined. High-grade ore in stringers, streaks, and bands occurs in serpentinized dunite. Chromite is also disseminated through the host rock. The deposit is cut by faults,

635 CHROMITE

A STATE OF THE PARTY OF THE PAR

which add difficulty to the mining operation. Allen 1 distinguishes at least six separate bodies in the Grev Eagle deposit. The crude ore ranges in grade from 5 to 25 percent Cr<sub>2</sub>O<sub>3</sub>. The mill heads averaged 12 percent Cr<sub>2</sub>O<sub>3</sub> in 1942.

Flow sheets of the mill, which has a 200-ton capacity, and a description of both the mining and milling operation have been published.2

The Pilliken mine in Eldorado County was the leading producer of chromite in the United States from 1938 to 1941, inclusive. In 1942, the operation ranked fourth among domestic producers. The Pilliken deposit was mined during World War I. After a long period of virtual inactivity, United States Chrome Mines, Inc., erected a mill in 1937. The property was leased by the Rustless Mining Corporation from 1939 to 1942. The owners resumed operation in September 1942 and are rehabilitating the mill.

Total shipments from the Pilliken mine during the entire period of production have been about 30,000 tons. Over 8,000 tons consisted of shipping ore containing about 43 percent Cr<sub>2</sub>O<sub>3</sub>, and the remainder was composed of concentrates, which in 1942 averaged 42 percent

Cr<sub>2</sub>O<sub>3</sub> and 18 percent FeO.

High-grade lenses of irregular shape and distribution, containing 40 to 50 percent Cr<sub>2</sub>O<sub>3</sub>, were mined in the past, according to Wells, who states that the future of the operation depends on blocking out large tonnages of milling ore, which carries about 10 percent Cr<sub>2</sub>O<sub>3</sub>.

In San Luis Obispo County the Castro mine was put into operation during 1942. Castro Chrome Associates, which operates the mine, erected a 125-ton mill at Goldtree Siding and began producing concentrates in May. The 1942 output amounted to 5,552 short tons averaging 41 percent Cr<sub>2</sub>O<sub>3</sub> and with a Cr: Fe ratio of 2.5:1. The Bureau of Mines and Geological Survey have explored the Castro and nearby deposits.4 The production from the district since 1870 has been about 50,000 tons of lump ore and about 7,000 tons of concentrates. Present reserves consist almost entirely of disseminated The crude ore mined in 1942 assayed about 20 milling-grade ore.

percent Cr<sub>2</sub>O<sub>3</sub>.

The High Plateau mine in Del Norte County, operated by Eugene R. Brown, is the leading domestic producer of high-grade ore. According to an analysis published by Allen,5 the ore contains 53.63 percent Cr<sub>2</sub>O<sub>3</sub> and 13.75 percent FeO. In the same county, Tyson Chrome Mines, Ltd., shipped 1,521 short tons of ore averaging 42.3 percent Cr<sub>2</sub>O<sub>3</sub> from the French Hill mine. Siskiyou County was the most active producing area in California, with over 20 shippers. The Cyclone Gap and Coggins mines, operated by J. K. Remsen, and the Come-Back mine (operators, Isgrig & Lilley) produced most from this county. Other properties in California with significant output were the McLaughlin & Applegarth mine in Tehama County, the Rivers mine of D. R. Moroney in Humboldt County, and the Victory

<sup>&</sup>lt;sup>1</sup> Allen, J. E., Geological Investigation of the Chromite Deposits of California: California Jour. Mines and Geol., vol. 37, No. 1, January 1941, pp. 133-134.

<sup>2</sup> Huttl, J. B., California's Chromite Assumes New Importance: Eng. and Min. Jour., vol. 143, No. 10, October 1942, pp. 43-46.
Mining World, California Chrome—Rustless Iron & Steel Corporation's Grey Eagle Mine: Vol. 4, No. 8, August 1942, pp. 3-8.

<sup>3</sup> Wells, F. G., and others, Chromite Deposits of the Pilliken Area, Eldorado County, Calif.: Geol. Survey Bull, 922-O, 1941, pp. 417-460.

<sup>4</sup> Department of Interior Information Service, Chromite Deposits near San Luis Obispo, Calif.: Press Notice 8533, December 1942, 2 pp.

<sup>4</sup> Allen, J. E., Work cited in footnote 1, pp. 117-118.

Chrome mine in Placer County. The last operation was described briefly by Huttl.<sup>6</sup> Space limitation precludes mention of the more

than 100 additional producing properties in California.

Montana.—The development of the Stillwater deposits in Montana is the largest project yet undertaken to procure chromite from domestic sources. Explored by Government agencies since 1939, the equipment of a mine and construction of a mill were begun in 1941. The Anaconda Copper Mining Co., designated as operators for the Government, produced the first concentrates in the 400-ton Benbow mill in March 1942. In the 10 months of operation during 1942 the output of the Benbow mill exceeded the recorded annual production from any domestic chromite property.

The Stillwater Complex is a stratiform body of ultramafic igneous rocks, 30 miles long and 1 to 5 miles wide. It contains chromite deposits in lenses and discontinuous layers that form horizons paralleling the layering of the complex. No high-grade ore is known to occur in the complex, according to Peoples and Howland, who have studied the deposits in detail. All the ore contains less than 40 percent Cr<sub>2</sub>O<sub>3</sub>.

The second-largest chromite operation in the United States in 1942 was also in Montana. The United States Vanadium Corporation mined ore from deposits in the vicinity of Red Lodge, Carbon County, beginning in October 1941. The chromite occurs in small serpentine intrusions on Hellroaring, Line Creek, and Silver Run Plateaus. Unlike the Stillwater deposits, those near Red Lodge are podlike. The grade of the ore ranges from about 40 to less than 25 percent Cr<sub>2</sub>O<sub>3</sub>, and the maximum Cr:Fe ratio is approximately 1.5:1. A mill was built at Red Lodge, and concentrates were first produced in March 1942. The milling operation was briefly described by Conwell.<sup>8</sup>

Oregon.—There were no large chromite producers in Oregon. Production increased from 840 short tons in 1941 to 2,683 tons in 1942. The Celebration mine in Grant County, operated by Hazeltine, Davis, and Byram, was the leading producer, with almost 500 short tons shipped. Next in order of shipments were the Sourdough and Hanenkrats mines of the Rustless Mining Corporation. The Sourdough mine in Curry County shipped 339 tons of chromite averaging 42.5 percent Cr<sub>2</sub>O<sub>3</sub>. The Hanenkrats mine in Grant County produced 248 tons of 40-percent ore. These three mines, with the Oregon Chrome and Black Beauty properties in Josephine

County, supplied more than half of the output of the State.

Other States.—In Idaho, production of chromite was reported for the first time. The ore was produced from an occurrence south of Riggins in Idaho County by A. Brandenthaler, who also conducted an operation in Baker County, Oreg. Production in Washington was limited to the Fortune Creek mine in Kittitas County, from which a small shipment was made by the Skipper Chrome Mining Co. In Alaska, the Chrome Queen Mining Co. produced ore on Red Mountain, Kenai Peninsula, but no shipments were made before the end of the year.

<sup>&</sup>lt;sup>8</sup> Huttl, J. B., Work cited in footnote 2, p. 46.

Peoples, J. W., and Howland, A. L., Chromite Deposits of the Eastern Part of the Stillwater Complex, Stillwater County, Mont.: Geol. Survey Bull. 922-N, 1940, pp. 371-416.

Conwell, C. N., Chrome Deposits at Red Lodge, Mont.: Mining Jour., vol. 26, No. 1, May 30, 1942, pp. 6-7.

#### EXPLORATION AND DEVELOPMENT

The large increase in domestic chromite production in 1941 and 1942 attests the amount of development in the last 2 years by private enterprise and Federal agencies. A few of the larger projects that have matured into active operations have been mentioned. In the near future important production is expected from the Mouat-Sampson deposit in the Stillwater district of Montana and from the Oregon beach sands. The Anaconda Copper Mining Co., agent for the Government, began mining on the Mouat-Sampson claims in the Stillwater Complex and prepared for concentrating the ores by building a mill to operate in 1943. This output will augment that from the Benbow mine and mill. In Oregon, beach sands in Coos County are the source of chromite that several companies plan to mine. The Krome Corporation has done experimental work since 1941 in this area. A concentrator is being erected at Bandon, Oreg., and a secondary chemical plant was planned at Marshfield. Two other companies—Humphreys Gold Corporation and Porter Bros. Corporation—were also actively engaged in developing production of chromite from the beach sands. In Alaska, preparations were made by the Alaska Juneau Mining Co. to mill chromite.

In 1942 the Bureau of Mines carried on an extensive development campaign throughout the Stillwater Complex in Montana. The Benbow and Mouat deposits were diamond-drilled, and further trenching and sampling of other areas were completed. As a result, several years' supply of chromite has been indicated ahead of present mining plans. Properties were also examined in California, Oregon, Georgia,

and Alaska.

The Geological Survey continued its detailed studies of the Stillwater Complex, Mont.; John Day district, Oreg.; Claim Point and Red Mountain, Alaska; and Oregon beach sands. The Red Lodge (Mont.) and Knik Valley (Alaska) deposits were mapped, and a magnetic survey was made of some of the Red Lodge deposits. Many brief examinations were also made, mainly in the Pacific States and Alaska, and inventories of the deposits of several counties in California were prepared. Two reports 9 on work previously done in the Red Bluff Bay area, Alaska, and in Stanislaus County, Calif., were published during the year.

Mineral dressing of Oregon beach sands was given special attention by the Bureau of Mines. Methods were developed by which concentration of chromite in products containing more than 40 percent Cr<sub>2</sub>O<sub>3</sub> can be made and other valuable minerals, such as zircon and garnet, recovered. Tests have shown that the Oregon beach chromite concentrates with low Cr: Fe ratio can be improved to a metallurgical-grade product by the Bureau of Mines reducing-roast acid-leach process. Pilot-plant tests with this process on Montana

concentrates were started at Boulder City, Nev.

<sup>&</sup>lt;sup>9</sup> Guild, Philip W., and Balsley, J. R., Jr., Chromite Deposits of Red Bluff Bay and Vicinity, Baranof Island: Geol. Survey Bull. 936-G, 1942, pp. 171-187.

Hawkes, H. E., Jr., Wells, F. G., and Wheeler, D. P., Jr., Chromite and Quicksilver Deposits of the Del Puerto Area, Stanislaus County, Calif.: Geol. Survey Bull. 936-D, 1942, pp. 79-110.

<sup>10</sup> Dasher, John, Fraas, Foster, and Gabriel, Alton, Mineral Dressing of Oregon Beach Sands, 1. Concentration of Chromite, Zircon, Garnet, and Ilmenite: Bureau of Mines Rept. of Investigations 3668, 1942, 19 pp.

#### USES AND CONSUMPTION

The market for chromite is created largely by the steel industry, which utilizes beneficial qualities imparted by the element chromium in certain alloy steels. Chromium is also employed in certain cast irons and nonferrous alloys. In addition to its value as a source of an alloying element, chromite is used widely for its refractory properties, especially in steel-making furnaces. Other applications of chromite are in chromium plating, pigments, dyes, and tanning.

Chromite is generally subjected to conversion (chemical or physical) processes to render it commercially usable. The most important of the initial conversion products is ferrochromium. This alloy is produced in various grades, which may be separated into two main groups upon the basis of carbon content. High-carbon ferrochromium, as sold in the United States, contains 4 to 6 percent C, whereas low-carbon grades range from 0.6 to 2 percent in maximum carbon. The chromium content of the alloy is roughly 60 to 70 percent, with higher percentages in the low-carbon grades.

As a refractory material, chromite is used in the form of bricks, cements, and plastics and also as crude lump or ground ore. chemical applications the main raw materials made from chromite are sodium and potassium bichromate.

The consumption of chromite usually is measured at the point at which the ore is converted to one of the products mentioned above.

New supply and distribution of chromite (ore and concentrates) in the United States, 1940-42, in short tons

	 	1		<del>: : -</del>
		1940	1941	1942
New supply: Domestic ore and concentrates Imports for consumption		2, 982 736, 612	14, 259 1, 115, 292	112, 876 980, 487
Total new supply Distribution:	 	739, 594	1, 129, 551	1, 093, 363
Consumption Exports  Total distribution	 	<sup>562, 915</sup> (1)  3 562, 915	800, 402 2 1, 906 3 802, 308	891, 952 4, 743 896, 698

The ore consumed can be classified into three grades, corresponding to the main categories of use. Chemical composition and physical properties distinguish these grades. The largest quantity consumed is metallurgical grade, followed in order by refractory and chemical In 1942 metallurgical and refractory ores constituted 87 percent of the total chromite used, and chemical ore comprised only The Bureau of Mines has conducted monthly surveys of chromite consumption (and also production) since 1939, originally for Federal defense agencies and now for the War Production Board. This record is probably the most complete ever made of the chromite industry in the United States and has proved of vital importance in maintaining a continual record of supply of a strategic mineral under The total consumption, 1940-42, is given in the accompanying table. Stocks of all grades of chromite owned by industry and

Data not available.
 Figures cover July to December; not separately classified before July.
 Incomplete; see footnote 2.

the Government aggregated over 1,250,000 tons at the end of 1942. Industry stocks have declined progressively in the last three years, but Government stocks increased greatly. In 1942, the Government stocks exceeded those in private control.

## IMPORTS AND EXPORTS 11

Chromite imports in 1942 fell short of the record set in 1941 by 12 Southern Rhodesia and Union of South Africa continued to be the main sources. Significant was the entry of U.S.S.R. into the list of countries from which chromite was obtained. The increase in

imports from Turkey and Canada was also noteworthy.

No chromium compounds have been imported since 1939. showing imports of such compounds from 1937 to 1939 is given in Minerals Yearbook, Review of 1940, page 591. Ferrochromium imports in 1942 came from Canada only. They totaled, in terms of chromium contained, 6 short tons of grades containing 3 percent or more carbon and 436 tons of grades with less than 3 percent carbon. No chromium metal was imported in 1942. Imports of ferrochromium and chromium metal from 1937 to 1941 are shown in a table in the chapter on Chromite in Minerals Yearbook, 1941.

Exports of chromite were first recorded separately by the Department of Commerce for July 1941; in the latter half of 1941 they totaled 1,906 short tons. During 1942, 4,743 tons were exported,

largely to Canada.

Crude chromite imported into the United States for consumption, 1938-42, by countries

	Gross weight (short tons)				1942		
Country					Shor	t tons	
	1938	1939	1940	1941	Gross weight	Cr <sub>2</sub> O <sub>3</sub> content	Value
North America: Canada Cuba Other	2 44, 273 66	73, 922 2, 130	209 58, 190	393 179, 944	13, 705 137, 826	6, 633 48, 396	\$372, 696 1, 330, 706
South America: Brazil	11, 200 3, 360	12, 320 1, 120	3, 125 15, 726 1, 120	6, 005 2, 199	6, 468	2, 983	84, 146
India Philippine Islands Turkey U. S. S. R	4, 537 87, 621 22, 839	18, 444 80, 544 18, 628	36, 561 175, 354 78, 491	10, 910 288, 411 61, 845	21, 316 30, 475 117, 396 30, 061	10, 604 12, 668 56, 032 15, 607	589, 272 277, 310 2, 297, 242 1, 200, 320
Africa <sup>1</sup> Oceania: Australia	188, 495	132, 421	319, 826 6	475, 377	541, 683	253, 615	6, 621, 994
New Caledonia 2	31, 942 394, 335	16, 082 355, 612	48, 004 736, 612	90, 208	980, 487	43, 292	1, 410, 473 14, 184, 159

Originated in Southern Rhodesia, Union of South Africa, and Sierra Leone; includes small amount in 1942 probably not produced in Africa. Recorded by Department of Commerce as imported from Union of South Africa, "Other British South Africa," "Other British West Africa," Mozambique, and Anglo-Egyptica Curlan. tian Sudan.

Recorded by Department of Commerce as French Oceania.

 $<sup>^{11}</sup>$  Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

# WORLD PRODUCTION

The progress of chromite production in foreign countries is difficult to appraise in wartime. The lack of information on production in the Axis-controlled countries is especially marked, but the same dearth of data is also noted for some of the United Nations. Thus, the level of production in U. S. S. R. is a matter of conjecture, although estimates suggest that that country is now and may well have been for several years the leading world producer. Reference to the accompanying world production table will show that no official statistics are available for any European or Asiatic country in 1941 and 1942. only is there an absence of statistics, but published comments on mining operations and developments are scarce. Next in order of output to U. S. S. R. are Southern Rhodesia, Union of South Africa, and Cuba. Turkey probably followed Cuba and slightly exceeded the United States in production during 1942. U. S. S. R. and Southern Rhodesia are the leaders in quantity of chromite produced and also in quantity of metallurgical ore. Union of South Africa is known as a source of chemical-grade chromite, whereas Cuba is principally a producer of refractory ore.

World production of crude chromite, 1938-42, by countries, in metric tons
[Compiled by B. B. Waldbauer]

Country	1938	1939	1940	1941	1942
North America:			904	0.150	6, 113
Canada Cuba Guatemala	33, 598 569	59, 562 564	304 52, 347 136	2, 152 163, 175 697 12	1 278, 000 529 17
Mexico	825 934	3, 672 3, 554	2, 705 4, 572	12, 935 5, 944	102, 399 5, 776
Europe: Albania	1, 745 42, 464 508	1 3, 000 4, 251 57, 091 371 (2)	(2) 6,000 4 33, 118 (2) 5 1, 118	(2) (2) (2) (2) (2) (2)	(3) (3) (3) (3) (3)
YugoslaviaAsia: Cyprus (shipments)India, British	5, 667 44, 858	59, 527 (2) 49, 925	6 58, 512 4, 775 (2) (2)	(2) (2) (2) (2)	
Japan Philippine Islands (exports) Syria and Lebanon Turkey. U. S. S. R.	213, 630	(2) 126, 749 (2) 191, 644 (2)	194, 393 (2) 4 110, 037 (2)	1 300, 000 (2) 1 100, 000 (2)	(3) (3) (3) (8) (3) (3)
Africa: Sierra Leone	505 186, 019	10, 755 139, 083 160, 014	17, 777 (2) 163, 646	(2) 7 322, 000 141, 884	(3) 7 335, 000 8 301, 073
Oceania: Australia: New South Wales New Caledonia	967 52, 216	108 52, 000	508 55, 790	356 1 45, 720	610 1 71, 120
	7 1, 128, 000	7 1, 167, 000	7 1, 300,000	7 1, 750, 000	(3)

<sup>1</sup> Estimated.

Process The main denosits in Brazil are in the State

Brazil.—The main deposits in Brazil are in the State of Baía The Cascabulhos, Pedrinhas, and Campinhos deposits near Campo Formoso and occurrences near Santa Luzia and Saúde contain the greater part of the reserves now known. Production has been small, probably slightly over 50,000 metric tons since 1918. Inadequate

<sup>&</sup>lt;sup>2</sup> Estimate included in total.

<sup>3</sup> Data not available.

<sup>4</sup> Exports.

<sup>&</sup>lt;sup>5</sup> Fiscal year ended July 31, 1940.

<sup>January to October, inclusive.
Partly estimated.
January to November, inclusive.</sup> 

641 CHROMITE

rail facilities to the port of Baía have hampered development, as has

the lack of water for milling in the Campo Formoso area.

A comprehensive discussion (with maps and analyses) of the chromite deposits in Baía was published in 1942 by Capper A. de Souza.<sup>12</sup> Reserves of high-grade ore at Cascabulhos and Pedrinhas are now estimated at 6,740 metric tons and probable ore is placed at 32,740 For the entire Campo Formoso area, there are also estimated to be about 200,000 tons of low-grade ores to a depth of 25 meters.

Bulgaria and Yugoslavia. The chromite deposits of the Skoplje region are included in the territory annexed by Bulgaria in the wartime dissolution of Yugoslavia. The addition of these resources will make Bulgaria the largest producer of chromite in Europe, assuming that the output is maintained at the former level. Pre-war Bulgaria was a very minor producer, mainly from deposits in the Krumovgrad district. The country's total output was 6,000 metric tons in 1940; Yugoslavia, on the other hand, produced about 60,000 tons of chromite

The Skoplje region contributed 97 percent of the total output of Yugoslavia before the war. 13 Allatini Mines, Ltd., a British firm, was the leading producer, operating several properties, including the Orašje mine and a washing plant at Raduša with a daily capacity of 100 tons of ore. A new plant was planned, probably near Skoplje, to treat ores from both Yugoslavia and Greece. The shipping product included high-grade ore, concentrates, and grained ore (defined 14 as "a coarse granular product, eliminated in the earlier stages of concentration, which is used as a refractory"). Small deposits, grading 25 to 30 percent Cr<sub>2</sub>O<sub>3</sub>, in serpentinized peridotite bodies predominate. The iron content ranges from 12 to 16 percent, and in the concentrates SiO<sub>2</sub> ranges from 4 to 6 percent. A detailed discussion of the Skoplje deposits summarized from various studies is presented by Sampson. 15

It is to be assumed that present operations are controlled by Germany, not only in the case of the Yugoslav deposits but also in those of Bulgaria proper. The supply from Yugoslavia is not as great as statistics of mine production would indicate, as most of the ore was concentrated. Approximately one-fourth of the crude ore is of shipping grade and part of this was treated with the washing ore.

Canada.—What has been called the greatest mineral discovery of the year in Canada was the finding of chromite in the Bird River area of southeastern Manitoba during the summer of 1942.16 Samples of the chromite had been assayed in 1935, but no interest was evinced in the occurrence at that time. The chromite-bearing rock occurs near Bird Lake and to the north near Euclid and Maskwa Lakes. Three chromite zones, several thousand feet long and having a total width of 100 feet, are recognized in a peridotite mass. The main occurrences west of Bird Lake are apparently separated by faulting of an anti-The tonnage of ore is said to be extremely large, clinal structure.

<sup>13</sup> Capper A. de Souza, H., Cromo na Baía: Depto. Nac. Prod. Min., Brazil, Bull. No. 54, 1942, 110 pp.
14 Mensebach, W., Bulgariens Zuwachs an Chromerzen: Metallwirtschaft, vol. 21, No. 25/26, June 26, 1942, pp. 386-387.
15 Allen, R., and Howling, G. E., Chrome Ore and Chromium: Imperial Inst., 1940, p. 75.
16 Sampson, E., Chromite Deposits in Ore Deposits as Related to Structural Features: Princeton Univ. Press, 1942, pp. 110-125.
18 de Wet, J. P., Chromite in Southeastern Manitoba: Canadian Min. Jour., vol. 63, No. 10, October 1942, pp. 657-658. Manitoba Chromite Find: Canadian Min. Jour., vol. 63, No. 11, November 1942, pp. 721-722.
18 Mining in Manitoba in 1942; Canadian Min. Jour., vol. 64, No. 2, February 1943, pp. 74-80.
19 Northern Miner, Important Chrome Find in Manitoba: Vol. 28, No. 24, September 3, 1942, pp. 1-2.

but the grade is low. The crude ore contains 16 to 20 percent Cr<sub>2</sub>O<sub>3</sub>, and preliminary tests indicate a possible concentrate of 36 to 40 percent with a Cr: Fe ratio of 1.25:1. At Euclid Lake the chromite bands are 26 feet wide, and the grade is reported to be higher than at Bird Lake.

The principal development work at Bird Lake has been done by God's Lake Gold Mines, Ltd., Gunnar Gold Mines, Ltd., and the Hudson Bay Mining & Smelting Co. Drilling has indicated ore to depths of 300 to 600 feet. Samples have been sent to the Department of Mines at Ottawa for testing. The studies are chiefly concerned with metallurgical problems posed by the low quality of the concentrates.

The Sterrett mine of Chromite, Ltd., at St. Cyr, Quebec, continued

operating in 1942. The 50-ton mill began producing concentrates in December 1941. A description of the occurrence of chromite in the Eastern Townships, by Denis, 17 includes a discussion of the Sterrett The Wartime Metals Corporation—a Canadian Government agency-had properties in this district examined, and one of themthe Bélanger deposit 18—is being reopened. A new mill was scheduled to begin operation in April 1943 at a daily rate of 600 tons. Exploration was also undertaken in the Gaspé region along a serpentine belt described as more than a mile long and several hundred feet wide. The assays reported a content slightly exceeding 40 percent Cr<sub>2</sub>O<sub>3</sub>. Chromium Mining & Smelting Corporation, manufacturers of ferroalloys at Sault Ste. Marie, Ontario, was said to be interested in the Gaspé occurrences.

Cuba.—An extensive preliminary report on the chromite deposits of Cuba was published by the Geological Survey of the United A few salient points are abstracted from this report. In 25 vears from 1916 onward, 795,277 short tons of Cuban chromite were imported into the United States. About 85 percent of this amount consisted of refractory ore, and the remainder was metallurgical ore. The Cuban deposits are irregular masses of variable size occurring in serpentinized peridotite belts along most of the northern coast. Mining has been limited to the eastern half of the island. chief sources of the Cuban ore have been the Camaguey district and eastern Oriente Province. The latter area includes the Mayari district, a source of metallurgical ore analyzing 55 to 58 percent Cr2O3 and with a Cr: Fe ratio of about 3.4: 1. Refractory ore from the Camaguey district contains 30 to 32 percent Cr<sub>2</sub>O<sub>3</sub>, 28 to 32 percent Al<sub>2</sub>O<sub>3</sub>, and about 5 percent SiO<sub>2</sub>. In most districts the grade of ore The field work of the Geological Survey was is fairly constant. expanded during 1942, especially in Oriente Province.

Greece.—The entire output of chromite in Greece is concentrated and shipped to the Krupp Works in Germany, according to a recent The operating properties are apparently the St. Athanasius mine at Xinia and the Apostolides mine at Tsagli in Thessaly, the Vrioni mine in Macedonia, and the Papostoriou mine near Kozani The monthly rate of production from the mines was in Thessalonikē. about 5,000 tons at the end of 1942.

Denis, B. T., The Chromite Deposits of the Eastern Townships of the Province of Quebec: Quebec Bureau of Mines, Ann. Rept., part D, 1931, pp. 95-98.

18 Denis, B. T., Work cited in footnote 17, pp. 83-87.

19 Thayer, T. P., Chrome Resources of Cuba: Geol. Survey Bull. 935-A, 1942, pp. 1-74.

643 CHROMITE

一般のできる 東京 のから からから かんかい かかからしてい かんかんかん

New Caledonia.—Although New Caledonia has not been the leading chromite producer since 1920, its output continues to be outstanding in quality. In 1942 the average grade of New Caledonia ore and concentrates imported into the United States was 53 percent Cr<sub>2</sub>O<sub>3</sub>. The annual rate of production is now estimated at over 75,000 short tons. Chromite has been produced in New Caledonia for 65 years, and the output has totaled approximately 2,000,000 tons. principal deposits are in the Tiébaghi Dome in the northern part of the island and have yielded more than 75 percent of the total output but currently are producing about one-half the annual total. Tiebaghi mine is one of the largest in the world, having produced roughly 1,500,000 tons of ore averaging 55 to 57 percent Cr<sub>2</sub>O<sub>3</sub>. Other properties in the Tiébaghi Dome are the Fantoche, Alpha, and Chagrin mines.

Turkey.—More space has been devoted to the subject of the disposition of Turkey's chromite after expiration of the Anglo-Turkish agreement on January 8, 1943, than to any other aspect of the world chromite industry. The German-Turkish agreements concluded in October 1941 and reported in the American and British press at that time were known to involve Turkey's chromite. The provisions apparently called for exchange of German war materials with a value of £T18,000,000, to be delivered during 1942, for 90,000 to 100,000 tons of chromite in both 1943 and 1944. The agreement was looked upon with misgiving, as it was stated that "The matter from the Allied viewpoint has been of importance, not so much from the angle of assuring supplies to Britain and her Allies, but of depriving the Germans of strategic material."20 Subsequent statements on the provisions of the agreement varied somewhat, so that a complete version as of the beginning of 1943 is quoted here:21

Between January 15 and March 31, 1943, Turkey and Germany will exchange goods to the value of £T55,000,000, including 45,000 tons of chrome on the Turkish side, and war material of the value of £T18,000,000 on the German side. It now seems to be established that the Germans will obtain supplies of chrome in proportions of the stable of tion to the amount of war material and other goods delivered by them to Turkey by the end of March 1943. According to the same agreement Germany may obtain from Turkey an additional 45,000 tons of chrome during the rest of 1943, and another 90,000 tons in 1944, against delivery of war material to Turkey, but these further deliveries become operative only if Germany has delivered by March 1943 the entire quantity of war material provided for in the first paragraph of the agreement.

Considerable skepticism was displayed as to Germany's ability to deliver goods acceptable to Turkey, and it was also suggested that Turkey was dissatisfied with goods so far received. There is nothing to indicate whether an actual exchange has taken place. It is noteworthy that Great Britain is reported to have resumed conversations with Turkey with a view to renewing their agreement. Also, Germany was reported in April 1943 to have negotiated further exchange of goods, but whether chromite was included is not known.

Production of chromite in Turkey has apparently decreased since 1938. One estimate from a German publication 22 gives 80,000 metric tons for 1941; at the same time it is suggested that an increase will result from the German agreement. It is stated that the chrome-

Metal Bulletin, Germany and Turkish Chrome: No. 2634, October 14, 1941, p. 7.

11 Chemical Age, Turkish Chrome: Vol. 48, No. 1229, January 16, 1943, p. 98.

12 Schuren, E., Die Metallwirtschaft in dem neuen Europa: Metallwirtschaft, vol. 21, No. 27/28, July 10, 1942, pp. 419-422.

mining areas in western Turkey are being exploited more fully again after a period of years during which the eastern deposits were most important.23 The Eti Bank, state mining bank of Turkey, was said to have received over £T1,000,000 to expand chrome mines.24

U. S. S. R.—In 1942 the United States imported 30,061 short tons of chromite averaging 52 percent Cr<sub>2</sub>O<sub>3</sub> from U. S. S. R. The principal deposits are in the Urals. Official information on production since 1936 has been entirely lacking. An unofficial British estimate 25 placed 1940 production at 400,000 tons of 48-percent ore. In 1940 a statement was made to the effect that production of 600,000 tons a year was planned by 1942.26 Reserves of chromite in the U. S. S. R. were estimated 27 to be 15,194,000 metric tons at the beginning of 1934. Of this total, 13,748,000 tons were in Saranovo, Sverdlovsk Province.

United Kingdom.—Refractory-grade chrome ore occurs on the island of Unst, Shetland Islands. It was mined during the last century and again in small quantities during and since World War I. In a recent report, Wilson 28 states that between 1922 and 1927 about 3,000 tons were produced; 323 tons were shipped in 1936, 710 tons in 1938, and 1,100 tons in the year ended July 31, 1940. The ore now worked contains about 26 percent Cr<sub>2</sub>O<sub>3</sub>. Typically the ore analyzes 25 to 45 percent Cr<sub>2</sub>O<sub>3</sub>, 10 to 20 percent SiO<sub>2</sub>, and 5 to 12 percent Al<sub>2</sub>O<sub>3</sub>.

Chrome-magnesite bricks produced from Shetland chromite have proved satisfactory in trials in open hearth and arc furnaces. The product compares favorably with brick made from Greek chrome ore.29

<sup>23</sup> Chemical Age, Work cited in footnote 21.
24 Metall und Erz, vol. 39, No. 8, April 1942, p. 153.
25 Foreign Commerce Weekly, Soviet Industries in the Urals: Vol. 7, No. 7, May 23, 1942, p. 9.
26 Friedensburg, F., Bodenschätze und Bergbau der Sowjetunion: Glückauf, vol. 76, 1940, pp. 317-339.
27 Volodomonov, N. V., Chromite: Min. Res. U. S. S. R., Cent. Geol. Prosp. Inst., Bull. 8, 1935.
28 Wilson, G. V., Talc, Other Magnesium Minerals and Chromite, Associated with British Serpentines: Geol. Survey, Great Britain, Wartime Pamphlet 9, 2d ed., October 1941, 27 pp.
29 Lynam, T. R., Chesters, J. H., Howie, T. W., and Jay, A. H., Shetland Chromite as a Refractory Material: Trans. British Ceram. Soc., vol. 41, pp. 27-44.

# NICKEL

By H. W. DAVIS

# SUMMARY OUTLINE

			Page	1 1 1 1 1 1 1 1 1 1		Page
Summary		 	 645	Foreign trade	 	647
Salient sta	tistics_	 	 645	World production.	 	648
Production			 646	1		

## SUMMARY

As a result of larger imports of nickel and the elimination of nonessential civilian and some military uses, conservation measures, and salvage of nickel-bearing scrap, the available supply was apparently adequate for vital war needs of the United States in 1942. So far as known, no shut-downs of essential war production due to lack of nickel supplies occurred during 1942. Nevertheless, so great was the demand that at no time during 1942 were domestic stocks of primary nickel more than a month's supply. An important conservation measure in the United States was the development of the National Emergency steels. These steels, some of which contain 0.2 to 0.7 percent nickel, were brought into being to spread the available alloys as widely as possible. No primary nickel is required for these steels. According to Butzner:

NE steels, with their huge savings of nickel and vanadium, were first produced in May, but the first heavy production was in August, when they made up 30 percent of the alloy production. In August a new and still more economical series was announced. The monthly production has since reached as much as 50 percent and will of necessity go higher. The proportion will fluctuate quite considerably month to month, depending on fluctuating emphasis on gun steels, for example, which are still high-nickel.

Salient statistics for nickel, 1938-42

	1938	1939	1940	1941	1942
United States: Production: Primary short tons Secondary do do	416 2,300	394 2, 920	554 4, 152	660 5,315	421 (1) 133, 062
Imports (gross weight) <sup>2</sup> do Exports (gross weight) <sup>3</sup> do Price per pound <sup>4</sup> cents	29, 546 6, 581 35	64, 796 10, 167 35	92, 468 11, 994 35	124, 130 7, 125 35	7, 068 35
Canada:         Production         short tons           Imports         do         Exports         do           World production (approximate)         do         do	105, 286 491 98, 852 127, 000	113, 053 697 117, 391 134, 000	122,779 (¹) (¹) 147,000	141, 129 (1) (1) 172, 000	141, 616 (¹) (¹) 174, 000

<sup>1</sup> Figures not yet available.
2 Excludes "All other manufactures of nickel"; weight not recorded.
3 Excludes "Manufactures"; weight not recorded.
4 Price quoted by International Nickel Co. of Canada, Ltd., for electrolytic nickel at New York, in 2-ton minimum lots.

<sup>&</sup>lt;sup>1</sup> Butzner, J. I., Nonferrous Metals: Iron Age, vol. 151, No. 1, January 7, 1943, p. 242.

Production of nickel in Canada in 1942 was about the same as in 1941, but in New Caledonia it declined slightly. The expansion program of the International Nickel Co. of Canada, Ltd. (announced in 1941), entailing an expenditure of \$35,000,000, has progressed to a point where it now assures an increase in productive capacity of 50,000,000 pounds of nickel annually over the 1940 rate of production. The expansion program of Falconbridge Nickel Mines, Ltd., begun in 1941, was completed about the middle of 1942.

In 1942, as heretofore, the domestic output of primary nickel was insignificant. In addition to the nickel produced as a byproduct in the electrolytic refining of copper and as secondary nickel, a little was

recovered as a byproduct of talc production in Vermont.

The St. Louis Smelting & Refining Co. did development work at its properties near Fredericktown, Madison County, Mo., where nickel and cobalt occur with lead, copper, and iron. The complexity of the ore presents a problem in metallurgy. However, the Bureau of Mines has studied the metallurgical problems involved, and the results of laboratory and pilot-plant tests at Rolla, Mo., indicate that fairly satisfactory recoveries can be made in cobalt-nickel and copperlead concentrates by selective flotation. Exploratory drilling was done by the Freeport Sulphur Co. on a nickel deposit near Riddle, Douglas County, Oreg. Some prospecting was reported at the long-

idle nickel property near Lancaster, Pa.<sup>2</sup>
Based upon the field work of the Bureau of Mines and upon data made available from other sources, a number of War Minerals Reports<sup>3</sup> on nickel deposits were prepared for the confidential use of Federal

war agencies.

The Geological Survey published reports describing the nickel deposits of Yakobi Island, Alaska, and near Gold Hill, Colo.5

The Dillon nickel prospect in Montana was described by Sinkler.

#### PRODUCTION

Domestic production of nickel is small and comprises secondary metals recovered from scrap-nickel anodes, nickel silver, and coppernickel alloys (including Monel metal), and primary metal recovered in copper refining and produced from ore and as a byproduct of tale production, as listed in the following table. Domestic primary nickel was recovered in 1942 as a byproduct in copper refining at Baltimore, Md., Laurel Hill, N. Y., Perth Amboy, N. J., and Tacoma, Concentrates containing 10 percent nickel and 0.78 percent cobalt were recovered as a byproduct of talc production in Vermont; however, none were shipped.

<sup>&</sup>lt;sup>2</sup> Skillings' Mining Review, vol. 31, No. 42, February 6, 1943, p. 2.
<sup>3</sup> Bureau of Mines, Big Stake Nickel Property, Custer County, Colo.: War Minerals Rept. 1, 1942, 7 pp. Bureau of Mines, St. Louis Smelting & Refining Co. Property, Fredericktown, Madison County, Mo. (Lead, Copper, Nickel, and Cobalt): War Minerals Rept. 3, 1942, 14 pp.

Bureau of Mines, Cle Elum Nickel-Iron Ore Deposit, Kittitas County, Wash.: War Minerals Rept. 27, 1442 1402.

<sup>1942, 10</sup> pp.
Bureau of Mines, Blewett Pass Nickel-Iron Ore Deposit, Chelan County, Wash.: WariMinerals Rept.

Bureau of Mines, Blewett Pass Nickel-Iron Ore Deposit, Uneian County, wash. warranter before 28, 1942, 10 pp.

4 Reed, J. C., and Dorr, J. V. N., Nickel Deposits of Bohemia Basin and Vicinity, Yakobi Island, Alaska:
Geol. Survey Bull. 931-F, 1942, 34 pp.

4 Goddard, E. N., and Lovering, T. S., Nickel Deposit near Gold Hill, Boulder County, Colorado: Geol. Survey Bull. 931-0, 1942, 14 pp.

5 Sinkler, Helen, Geology and Ore Deposits of the Dillon Nickel Prospect, Southwestern Montana: Econ. Geol., vol. 37, No. 2, March-April 1942, pp. 136-152.

THE PROPERTY OF THE PARTY OF TH

THE ASSESSMENT OF THE PROPERTY OF A

Nickel produced in the United States, 1938-42

	Primary (s	hort tons) 1	Secon dary 2		
Year	Byproduct in copper refining 3	Other 4	Short tons	Value	
1938	416 394 554 619 416	41 5	2, 300 2, 920 4, 152 5, 315	\$1, 610, 000 2, 044, 000 2, 906, 400 3, 720, 500 (5)	

# FOREIGN TRADE 7

The nickel imported into the United States in 1942 comprised chiefly metallic nickel, matte, and oxide. As heretofore, Canada was the chief source of the imports; it supplied 61,003,121 pounds of matte, 161,151,775 pounds of metallic nickel, 23,837,605 pounds of oxide, and 1,990,000 pounds of residues. The matte from Canada, which contains approximately 55 percent nickel and 25 percent copper, is refined to Monel metal and other products at the plant of the International Nickel Co., Inc., Huntington, W. Va. New Caledonia supplied 19,472,399 pounds of matte; it contains about 78 percent nickel and is also refined at Huntington, where a new plant was completed in 1941 for refining matte from New Caledonia and elsewhere. About 7,200 short tons of nickel were produced at Huntington from New Caledonian matte in 1942. Cuba supplied 117,602 pounds of ore (presumably); the United Kingdom 117,304 pounds of oxide and 383,170 pounds of metallic nickel; and Mexico and Switzerland 40,007 and 178 pounds, respectively, of metallic nickel.

The nickel content of the unmanufactured nickel products imported into the United States is estimated at 228,550,000 pounds in 1942, as compared with 212,363,000 pounds in 1941. Imports of

nickel in 1942 established a new peak.

Exports of nickel comprise largely products manufactured from imported raw materials. Exports of metallic nickel, Monel metal, alloys, and scrap increased 9 percent over 1941, whereas nickel-chrome electric resistance wire almost doubled. Exports of nickel silver, however, declined 91 percent. The United Kingdom (7,927,986 pounds), U. S. S. R. (3,076,692 pounds), and Canada (2,079.398 pounds) were the chief markets for nickel, Monel metal, alloys, and scrap in 1942.

Bureau of Mines not at liberty to publish value.
 Nickel recovered as metal and in alloys and salts.
 Nickel content of nickel salts and metallic nickel.
 Nickel content of matte produced from ore and of concentrates produced as byproduct of talc.
 Figures not yet available; they will be found in chapter on Secondary Metals—Nonferrous.

<sup>7</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Nickel (excluding residues) imported for consumption in the United States, 1940-42. by classes

	19	40	19	41	1942		
Class	Pounds	Value	Pounds	Value	Pounds	Value	
Unmanufactured:  Nickel ore and matte.  Nickel pigs, ingots, shot, etc.  Nickel bars, rods, tubes, etc.  Nickel oxide.  Manufactured:  Nickel silver or German silver in sheets, strips, rods, and wire.  All other manufactures of nickel.	34, 889, 970 140, 625, 658 434, 139 8, 986, 834 153	193, 284 1, 692, 961	18, 377, 937	37, 429, 028 227, 319	161, 202, 200 372, 930 23, 954, 909	40, 588, 948 174, 511	
		41, 745, 788		51, 967, 548		56, 403, 305	

<sup>1</sup> Quantity not recorded.

# Nickel exported from the United States, 1940-42, by classes

Class	19	40	19	)41	1942	
	Pounds	Value	Pounds	Value	Pounds	Value
Ore, concentrates, and matte Alloys and scrap containing nickel (including Monel metal) Metal in ingots, bars, sheets, etc Manufactures Nickel-chrome electric resistance wire Nickel silver or German silver, crude, scrap, or bars, rods, etc Nickel salts and compounds	(1) 640, 816 1, 502, 071	1, 393, 636	(1)		104 8, 996, 413 4, 251, 948 (1) 668, 194 155, 282 64, 981	3, 472, 575 1, 947, 597 3, 753, 594 792, 255 94, 563

## WORLD PRODUCTION

Because of restriction on the publication of statistics by many governments, few figures have become available since 1939.

World production of nickel (content of ore), 1937-42, by countries, in metric tons 1

	Сощр	ned by B. B	. waldbauer	1		
Country 1	1937	1938	1939	1940	1941	1942
Australia Brazil Burma Canada Egypt Germany Greece Italy Morocco, French Netherlands Indies Now Caledonia Norway Southern Rhodesia Union of South Africa U. S. S. R	957 68 132 11, 600 877 4	20 375 959 95, 514 3 350 1, 207 4 150 163 4 500 11, 700 1, 245 76 44 2, 500	25 921 102,559 (2) (2) (3) (4) (2) (4) (5) (4) (4) (4) (4) (5) (6) (6) (6) (7) (8) (9) (9) (9) (9) (9) (9) (9) (9) (9) (9	(2) (2) (3) (111, 383 (2) (2) (2) (2) (2) (2) (3) (2) (2) (3) (4) (535 (2) (2) (4) (4) (4) (4) (4) (5) (5) (6) (7) (8) (9) (9) (9) (9) (9) (9) (9) (9) (9) (9	(2) (2) (2) (2) (2) (2) (2) (3) (2) (3) (4) (5) (6) (7) (9) (9) (9) (9) (9) (9) (9) (9) (9) (9	(2) (2) (2) (128, 47) (2) (2) (2) (2) (2) (2) (2) (2) (2) (2
	120, 100	115, 500	4 122, 000	4 133, 000	4 156, 000	4 158, 000

<sup>&</sup>lt;sup>1</sup> In addition to countries listed, Finland and Japan produce nickel, but data of output are not available.
<sup>2</sup> Data not yet available; estimate included in total.

Quantity not recorded.
 Not separately classified.
 Figures cover September to December; not separately classified before September 1.

Excludes small quantity produced in British Columbia.
 Estimate.

Byproduct in electrolytic refining of copper. Includes also—1941: Small quantities produced from ore and as byproduct of tale; 1942: Small quantity as byproduct of tale.

649 NICKEL

Brazil.—The nickel deposits at São José do Tocantins, State of Goyaz, and at Livramento, State of Minas Gerais, have been described in considerable detail by Wright and Pardee.8 A brief summary of the deposits will be found in Minerals Yearbook, 1941.

According to the American Smelting & Refining Co.:

The company acquired a 50-percent interest, together with a term management contract, in a nickel property in the State of Goyaz, Brazil. This property was corefully examined by four of the company's senior engineers. Their reports indicate there is a very large tonnage of ore, containing a percent of nickel that should assure a profitable operation. The ore is refractory, but the company's research department succeeded in working out a process which will recover the nickel. The mine contains cobalt in commercial amounts, and extraction of this metal will probably begin in advance of the nickel operation. It is planned first to erect at Perth Amboy (N. J.) a small pilot plant, and with knowledge gained therefrom to design a commercial plant to be constructed at the property during 1944, although as regards completion much will depend on nonpredictable factors, such as ability to obtain the necessary material, equipment, and shipping facilities.

Canada.—Virtually all the Canadian output is derived from the copper-nickel ores of the Sudbury district, Ontario; and two companies—International Nickel Co. of Canada, Ltd., and Falconbridge Nickel Mines, Ltd.—are the principal producers. Production in Canada was 141,616 short tons in 1942, compared with 141,129 tons in 1941 and 122,779 tons in 1940.

The International Nickel Co. of Canada, Ltd., 10 stated:

It is gratifying to report, as forecast a year ago, that the increase in production of nickel in all forms of 50,000,000 pounds over the 1940 output has been realized. Work on production expansion has progressed according to schedule and is largely All of the company's works ran continuously throughout the year and, considering the shortage of labor and the difficulty in securing supplies, the operating results were satisfactory.

# According to Falconbridge Nickel Mines, Ltd.: 11

All treatment plants were operated at maximum capacity throughout the year, though with considerable difficulty at times due to the construction programs which were being carried out. On the whole the result achieved may be viewed with satisfaction, since a substantial increase both in tonnage treated and in production is again recorded. The program to expand capacity begun in 1941 was completed by the middle of the year. This project included additional crushing equipment at the shaft head; some increase in storage-bin capacity and handling equipment; grinding mills; flotation equipment and additions to thickening and filtering capacity in the mill; additional sintering capacity and changes in the smelting plant, together with the provision of added and improved change-house facilities both at mine and smelter.

The Alexo nickel property, which produced nickel during the First World War, is again to be a contributor, arrangements having been made for the sale of the ore.12

According to the Northern Miner: 13

Nickel Offsets, Ltd., is proceeding with the deepening of the shaft at its property in Foy and Bowell Twps., Sudbury district. In previous work the shaft was sunk to 530 feet, with a large amount of development carried out at the 200, 350, and 500-foot levels. It is now proposed to go down to 1,250 feet and to cut stations at 150-foot intervals as sinking proceeds.

<sup>8</sup> Wright, C. W., and Pardee, F. G., The Nickel-Cobalt Deposit at São José do Tocantins, State of Goyaz, Brazil: Ms. Rept., June 4, 1941, 22 pp.; The Nickel Deposit at Livramento, Minas Gerais, Brazil: Ms. Rept., June 14, 1941, 10 pp.

9 American Smelting & Refining Co., 44th Annual Report: 1942, p. 3.

10 International Nickel Co. of Canada, Ltd., Annual Report: 1942, p. 4.

11 Falconbridge Nickel Mines, Ltd., 14th Annual Report: 1942, pp. 1-10.

12 Canadian Mining Journal, vol. 63, No. 12, December 1942, pp. 818.

13 Northern Miner, vol. 28, No. 39, December 17, 1942, p. 8

A deposit of high-grade nickel ore has been developed at the Moose mine, near Sudbury, by the Ontario Nickel Corporation; equipment has been partly installed for a daily output of 300 tons. 14

Cuba. - According to the Freeport Sulphur Co., which, through its subsidiary, Nicaro Nickel Co., is constructing a plant in Cuba for the

production of nickel: 15

A great deal of time and thought of this organization has gone into pushing the construction of this plant during the past year. It is difficult to say when production will start, because the commencement of operations is dependent upon the priorities which we may receive for the equipment necessary for the completion of the plant.

Finland.—A Swedish engineering firm is erecting automatic heating apparatus for the mining town of Kilosjoki, where the mines of Petsamo Nikkeli O/Y are situated. The town will shelter the 3,000

workers and officials of the nickel-mining company.

With the assistance of German materials and engineers, the mine (Petsamo), which was considerably damaged in the first Russo-Finnish conflict, has been restored and production resumed.<sup>17</sup> nickel deposit has been discovered in central Finland at Nivala; preparations for production are in progress.

A plant now under construction by the Outukumpu O/Y at Pori, the first of its kind in the country, will eventually supply 400 tons of nickel a year. 18 Meanwhile, the company is producing copper-nickel ore at the rate of 18,000 tons a year, most of which is probably being

sent to German refineries.

New Caledonia.—New Caledonia ranks second in world production The Société Le Nickel owns a number of properties in various parts of the island, but the most important are those around Thio on the east coast and around Voh and Koné on the west coast. The smelter, comprising four furnaces, is at Noumea and produces a matte containing 77.5 to 78 percent nickel for export. About 90 percent of the ore smelted comes from the mines of the company, and 10 percent is purchased from small miners. For several years previous to the war, shipments of ore were made to Germany and Japan by the small miners.

Nickel ore treated in and matte exported from New Caledonia, 1938-42

	Ore tr	eated	Matte exported (long tons)							
Year	Long tons	Percent nickel (average)	Australia	Belgium	France	United States	Total			
1938 1939 1940 1941 1942	241, 131 248, 020 296, 246 292, 309 264, 752	4, 5 4, 0 3, 5 3, 5 3, 5	1 3, 143 2 394 738	4, 194 2, 569	3,710 6,586 1 4,724	7, 756 6, 417	7, 90- 9, 15- 7, 86- 8, 15- 7, 15-			

Of these quantities, 1,019 tons destined to Australia and 883 tons destined to France were reexported to the United States in 1941.
 Reexported to the United States in 1942.

<sup>Engineering and Mining Journal, vol. 143, No. 5, May 1942, pp. 95-96.
Freeport Sulphur Co., 30th Annual Report: 1942, p. 5.
Metal Bulletin (London), No. 2671, February 24, 1942, pp. 9-10.
Schuren, E., Metal Industry in New Europe: Metallwirtschaft, vol. 21, No. 27/28, July 10, 1942, pp.</sup> 419-422. <sup>18</sup> Chemical Age (London), vol. 47, No. 1214, October 3, 1942, p. 306-

# **COBALT**

By H. W. Davis

#### SUMMARY OUTLINE

P	age	P	'age
Summary	651	Uses	653
Production	651	World production	653
Foreign trade	653		

#### SUMMARY

Despite prohibitions and limitations on the use of cobalt for many purposes, total consumption in the United States was about 12 percent greater in 1942 than in 1941. There was a marked increase in consumption of cobalt in stellite and stellite-type alloys, magnets and magnet steels, and carbide-type alloys; but this gain was partly offset by a decline in the amount used in ground-coat frit, pigments, and driers. Although domestic production of cobalt made considerable gain in 1942, most of the demand, as heretofore, was supplied by imports, mainly in the form of alloy from Belgian Congo and ore from Canada. The domestic ore, which averages about 1.4 percent cobalt, is processed to metal, oxide, and hydrate at Wilmington, Del. The alloy from Belgian Congo contains about 40 percent cobalt and is converted to metal and oxide at Niagara Falls, N. Y., and to oxide, sulfate, catalytic salts, or driers at Chicago, Ill., Cincinnati and Cleveland, Ohio, Elizabeth, N. J., New Brighton, Pa., and Richmond, Calif. The Canadian ore, which averages about 11 percent cobalt, is processed to cobalt oxide and other products at Cincinnati, and to cobalt-nickel oxide at Canonsburg, Pa., and Cleveland, Ohio. A new cobalt-nickel plant was being built at Cleveland, Ohio, to treat Burmese speiss, which contains about 7 percent cobalt, 30 percent nickel, 40 percent arsenic, and 10 percent copper. The products contemplated are cobalt oxide, nickel oxide, copper oxide or hydroxide, and calcium arsenate. It is expected that the plant will be ready for operation about May 15, 1943. In the plant, room is provided for the addition at a later date of smelting equipment for treating Canadian concentrates containing about 10 percent cobalt, 3 percent nickel, and 25 percent arsenic.

Domestic quotations for metal in 100-pound lots and for black oxide

Domestic quotations for metal in 100-pound lots and for black oxide in 350-pound lots remained unchanged throughout 1942 at \$1.50 and \$1.84 a pound, respectively. These prices have been in effect since the

latter part of October 1939.

## **PRODUCTION**

Though comparatively small, production of cobalt ore in the United States increased considerably in 1942; the Bethlehem Steel Co., Beth-

and the second s

THE REPORT OF THE PARTY OF THE

lehem, Pa., was again the chief producer and shipper. The cobalt (averaging about 1.4 percent) is contained in the sulfides that accompany the magnetite mined at Cornwall, Pa. The Eastern Magnesia Talc Co., Inc., Burlington, Vt., recovered 50 short tons of concentrates, containing 0.78 percent cobalt and 10 percent nickel, as a byproduct of froth flotation of talc. The Sullivan Mining Co., Kellogg, Idaho, recovered 64 short tons of residue, containing 5.66 percent cobalt, at its electrolytic zinc plant. At the Columbia mine near Goodsprings, Nev., Otto F. Schwartz did some development work and shipped 1

short ton of concentrates averaging 6.96 percent cobalt.

The St. Louis Smelting & Refining Co. did development work at its properties near Fredericktown, Madison County, Mo. By December 1942, a new shaft had been sunk to 400 feet; two additional shafts are contemplated in 1943. At these properties cobalt and nickel occur with lead, copper, and iron, but the complexity of the ore presents a problem in metallurgy. The property was visited by a Bureau of Mines engineer in August 1942, and a report 1 was prepared showing the production possibilities of the deposits and indicating the metallurgical testing undertaken by the Bureau to determine a suitable treatment method. Results of the Bureau's laboratory and pilot-plant tests at Rolla, Mo., indicate that fairly satisfactory recoveries can be made in copper-lead and cobalt-nickel concentrates by selective flotation.

After examinations in 1941 and June 1942, the Bureau of Mines in August 1942 undertook an exploration and ore-testing project on a group of claims of the Uncle Sam Mining & Milling Co., Inc., in the Blackbird district in east-central Idaho. By the end of 1942, sampling of underground workings had established a moderate tonnage of positive ore averaging 2.06 percent copper and 0.29 percent cobalt, with additional values in gold and silver. This sampling also provided a basis for estimating a considerable tonnage of geologically inferred Further surface and underground exploration, including sampling, drifting, and crosscutting, are planned for 1943. Ore testing of samples at the Salt Lake City Experiment Station of the Bureau has shown that good recovery of cobalt, copper, and gold can be made by bulk flotation in a concentrate that is of low grade with respect to Fair recovery of cobalt in a separate cobalt concentrate of better grade was obtained by selective flotation and tabling. sults of the preliminary examinations and plans for Bureau exploration are discussed in a recent report.2

Small amounts of cobalt are associated with many manganese ores, but the cobalt is not extracted in the usual metallurgical and chemical processing of these ores. The Bureau of Mines determined early in its development of the electrolytic manganese process that most of the cobalt goes into solution together with the manganese in the leaching step and is precipitated with other impurities upon purification of the leach solution. In view of this potentially large source of cobalt and the difference of opinion as to whether leach solutions containing cobalt can be purified sufficiently for satisfactory electrodeposition of manganese, tests were made at the Boulder City (Nev.) electrolytic manganese pilot plant of the Bureau on the separation and electrodeposition

<sup>&</sup>lt;sup>1</sup>St. Louis Smelting & Refining Co. Property, Fredericktown, Madison County, Mo.: Bureau of Mines War Minerals Rept. 3, 1942, 14 pp.

<sup>2</sup>Blackbird District, Lemhi County, Idaho; Bureau of Mines War Minerals Rept. 78, 1943, 8 pp.

COBALT 653

of manganese and cobalt from manganese electrolytes. These tests proved that appreciable concentrations of cobalt in manganese solutions can be eliminated sufficiently to allow satisfactory electrodeposition of manganese and that recovery of cobalt from the sludge residue of the manganese-electrolyte purification is feasible.

## FOREIGN TRADE 3

Imports.—Imports of cobalt into the United States in 1942 were 30 percent less than those in 1941, which, however, was a peak year. The chief source of imports in 1942 was Belgian Congo, which supplied 7,928,952 pounds in the form of an alloy containing 3,208,687 pounds of cobalt. Canada supplied 148,304 pounds of cobalt (metal) and 834,797 pounds of ore containing 91,597 pounds of cobalt, and the United Kingdom 200 pounds of salts and compounds of cobalt.

Cobalt ore, metal, oxide, and other compounds of cobalt imported for consumption in the United States, 1938-42

	Ore		м	etal	Oz	ride	Suli	ate	Other sa compo		
Year	Pou	nds						. Teat : :			
	Gross weight	Cobalt content	Value	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value
	449, 984 611, 083 10, 497, 719 12, 414, 314 8, 763, 749	(1) 4, 326, 929	3, 660, 869 4, 587, 787		842, 288	680, 644 756, 759 38, 002	944, 836 1, 124, 554	75, 290 11, 468		1,374	\$98 3, 405 885 448

<sup>1</sup> Data not available.

Exports.—Exports of cobalt were 118,866 pounds valued at \$162,039 in 1942. From July to December 1941 exports totaled 34,341 pounds valued at \$37,670; exports of cobalt before July 1, 1941, are not separately recorded.

## USES

The largest single use of cobalt is in stellite or stellite-type alloys, and such alloys absorbed about 39 percent of the total cobalt consumed in 1942. Other important uses of cobalt are in magnets and magnet steels, high-speed steels and other cutting-tool materials, valve steel, welding rod, and carbide-type alloys; these outlets comprised about 44 percent of the cobalt consumed in 1942. Smaller quantities of cobalt are employed in the ceramic industry, in the preparation of driers, in electroplating, as a catalyst, and for a variety of other uses. Of the total cobalt consumed in 1942, 10 percent was used in driers, 5 percent in ceramics, and 2 percent for electroplating, catalyst, and other applications.

#### WORLD PRODUCTION

As cobalt production data for many countries are lacking, it is impossible to prepare an accurate statement of world output. Never-

<sup>&</sup>lt;sup>3</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

theless, world production for 1942 is estimated at 5,000 to 5,500 metric With the occupation of French Morocco, the United Nations l about 85 percent of the world output. The following table control about 85 percent of the world output. shows world production by countries, 1937-42, insofar as statistics are available.

World production (partly estimated) of cobalt, 1937-42, by countries, in metric tons 1

[Compiled by B. B. Waldbauer]

		Cobalt content						
Country 1	Cobalt-bearing material	1937	1938	1939	1940	1941	1942	
Australia Belgian Congo Bolivia (exports) Burma Canada Morocco, French Northern Rhodesia United States	Cobalt ore	(2) 1,500 (3) 4 298 230 581 4 578	(2) 1, 532 4 238 208 720 4 1, 073	(2) (2) 4 229 332 719 4 1, 598	(2) (2) 218 360 700 (2) (5)	(3) (2) 2 73 119 700 (2) (5)	2, 200 (2) (3) 40 (2) (5)	

<sup>&</sup>lt;sup>1</sup> In addition to the countries listed, Brazil, Chile, China, Finland, Germany, Italy, Japan, and Mexico produce cobalt, but production data are not available. The world total for 1942 is estimated at 5,000 to 5.500 tons.

Belgian Congo.—Belgian Congo is the world's chief source of cobalt. Cobalt is mined as such and as a high-grade copper-cobalt-ore. Cobalt also occurs with sulfide and carbonate copper ores, from both of which partial recovery is made by concentration. Production data have not been published since 1938, when 1,532 metric tons were produced. Since then, however, it has been reported that further reserves of rich cobalt minerals have been discovered, the Kabolela cobalt mine has been developed, a concentrator has been installed, and a fourth electric furnace added. As a consequence, production undoubtedly has increased considerably and may have reached 2,200 tons in 1942. additional electric furnaces were under construction in 1942 which, when in operation, should increase production to above 3,000 tons.

Brazil.—Cobalt is associated with nickel at Jacuba, São José do Tocantins, State of Goyaz. The American Smelting & Refining Co. (New York, N. Y.) recently acquired a 50-percent interest in the Companhia Niquel Tocantins and will construct a pilot plant at Perth Amboy, N. J., to refine nickel from ore from the properties in the State of Goyaz. Extraction of cobalt probably will be begun in advance of the nickel operation.

French Morocco.—French Morocco ranks third as a world producer With the occupation of this country by the United Nations, the Axis-controlled countries lost access to its cobalt supplies, which have been allocated to the United States by the Combined Raw Materials Board.

Northern Rhodesia.—Northern Rhodesia is the second-largest producer of cobalt in the world. Cobalt in association with copper is produced at the Nkana mine of the Rhokana Corporation, Ltd. The

<sup>500</sup> tons.

2 Data not available.

3 Less than 1 ton.


4 Year ended June 30 of year stated.

5 Bureau of Mines not at liberty to publish figures.

COBALT 655

copper ore contains 0.02 to 0.5 percent cobalt in the form of sulfide, and by special processes, involving differential flotation of certain of the ores and treatment of the converter slags, a rich cobalt-iron-copper alloy is produced. The alloy contains about 40 percent cobalt and at present is exported to Canada for refining. Recent production figures are not available, but in a statement circulated with the annual report of the Rhokana Corporation, Ltd., for the year ended June 30, 1942, it was reported that the largest possible amount of cobalt had been produced and was still being produced, in spite of the many difficulties that had to be overcome. During the year ended June 30, 1939, alloy containing 1,598 metric tons of cobalt was produced.

<sup>&</sup>lt;sup>4</sup> Deans, T., The Mineral Resources of Northern Rhodesia: Min. Jour. (London), vol. 220, No. 5612, March 13, 1943, p. 130.



# **MOLYBDENUM**

By Frederick Betz, Jr., and Alice P. van Siclen

#### SUMMARY OUTLINE

	Page		Page
Summary	657		374,50
Salient statistics	657	Exploration and development	661
War regulations	. 658	Consumption and uses	661
Market		Imports and exports	662
United States	. 658	World production	663
Producers in 1942	658		

#### SUMMARY

Molybdenum is produced in many parts of the world, but compared with the United States there is no producer of importance. The combined output of all other countries is less than 10 percent of the world total, and most of that comes from Western Hemisphere countries and Norway and French Morocco. Reliable estimates of output in European and Asiatic countries under the influence of the Axis are not available, but no established producer of any note,

except Norway, would fall in that category.

In 1942 all earlier records for domestic production of molybdenum were exceeded. Output of molybdenum in ore and concentrates in the United States rose 42 percent to 57,077,000 pounds; the Climax Molybdenum Co. produced approximately 73 percent of the total, and all but about 3 percent of the remainder was byproduct recovery from three copper operations. Imports of molybdenum ordinarily are a negligible factor in the available supply; although still relatively very small, in 1942 they amounted to 755,950 pounds in ores and concentrates, the greater part of which came from Chile. Exports increased 52 percent in 1942 to 11,617,517 pounds.

Molybdenum has been used so extensively to replace less abundant steel-alloying metals that measures for its conservation have been adopted by placing it under complete allocation (WPB General Preference Orders M-110 and M-110-a) and by reducing the Mo content of alloy steels in the new NE (National Emergency) series.

Salient statistics of the molybdenum industry in the United States, 1940-42

	1940	1941	1942
Concentrates: Production short tons	33, 128	38, 962	56, 239
Molybdenum contained pounds Shipments (including exports) short tons.	34, 313, 000 24, 300	40, 162, 000 36, 894	57, 077, 000 65, 329
Molybdenum contained:			50. 85
A veragepercent_ Totalpounds	52. 12 25, 329, 000	38, 200, 000	66, 437, 000
Value 1short tons_	\$17, 189, 000 6, 339	\$25, 883, 000 7, 673	\$47, 299, 000 10, 731
Molybdenum contained pounds Value	6, 584, 714 \$4, 904, 000	7, 640, 330 \$5, 379, 367	11, 617, 517 \$7, 958, 662
Imports for consumption (molybdenum contained): Pounds		4, 300	755, 950
Value		\$2,898	\$554, 232

<sup>1</sup> Estimate by Bureau of Mines.

## WAR REGULATIONS

All forms of molybdenum, including scrap, were placed under complete allocation by War Production Board General Preference Order M-110, dated March 18, 1942 (effective May 1). On August 8 this order was amended to permit the melting of molybdenum only after approval of melting schedules, as provided in Order M-21-a, and to extend the effective time of the order until revoked. The original provision exempting users of less than 50 pounds monthly from reporting their requirements was modified on November 6 by an amendment (M-110-a) permitting, under certain conditions, deliveries up to 500 pounds of contained molybdenum in any one month without allocation. Melters whose requirements are not large may use up to 500 pounds monthly without submitting melting schedules to the War Production Board. On January 9, 1943, secondary molybdenum chemicals were removed from the M-orders on molybdenum.

An order of the Board of Economic Warfare provided that, as of July 9, 1942, molybdenum ore and concentrates, products, alloys, and scrap could be exported under general license only to Canada and Newfoundland. An individual license is required for clearance of exports of these molybdenum-bearing materials to all other foreign

countries.

## MARKET

The quoted price for molybdenum ore refers to molybdenum in concentrates containing 90 percent MoS<sub>2</sub>. The price has held at 45 cents per pound (equivalent to 75 cents per pound of molybdenum contained) f. o. b. mines for several years. In practice, the price is said to vary with the grade. The molybdenite concentrates are shipped largely to processing plants for conversion to molybdenum oxide, calcium molybdate, ferromolybdenum, etc. The prices of the principal molybdenum products are based on a pound of contained molybdenum, f. o. b. producer's plant. Molybdenum oxide and calcium molybdate are priced at 80 cents and ferromolybdenum at 95 cents.

#### UNITED STATES

#### PRODUCERS IN 1942

Only seven ore deposits were exploited actively during 1942 for their molybdenum content. One of them, the Climax deposit, is the world's largest molybdenum producer. All but two are operated mainly for their yield of other metals. Among the group that produces molybdenum as a byproduct is the Bingham copper deposit, second-largest producer of molybdenum in the United States. The chief ore of molybdenum is molybdenite (MoS<sub>2</sub>); wulfenite (PbMoO<sub>4</sub>), once mined from several deposits in southwestern United States, is now extracted at a single mine.

Domestic shipments of molybdenum in ore and concentrates in 1942, amounting to 66,437,000 pounds, were 74 percent greater than

in 1941 and represent about 23 percent of the total shipments since 1918.

Molybdenum in ore and concentrates shipped from mines in the United States, 1914-421

Year	Pounds	Value 2	Year	Pounds	Value <sup>2</sup>
1914-18 1919-23 <sup>3</sup> 1924-28 1929-33 1934-38	1, 601, 643 355, 493 8, 498, 343 18, 954, 917 94, 077, 000	\$2,070,213 370,371 6,160,304 11,406,000 64,244,000	1939 1940 1941 1942	32, 415, 000 25, 329, 000 38, 200, 000 66, 437, 000	\$22, 157, 000 17, 189, 000 25, 883, 000 47, 299, 000
		01,211,000	1914-42	285, 868, 396	196, 778, 888

For shipments by years, 1914-38, see chapter of this series for 1941.
 Largely estimated by Bureau of Mines.
 No shipments in 1920 and 1921.

Climax and Questa are the only molybdenum deposits now operated solely for their content of this metal. In 1942 Climax produced 73 percent of the total United States output of molybdenum. is a very much smaller operation but has been a consistent producer for 20 years and thereby has contributed substantially to the domestic production of molybdenum during that period.

The Climax deposit in Colorado has been discussed extensively in literature, as have the various aspects of the mining and milling operation. In 1942, Vanderwilt summarized the ore occurrence. and a review of Climax is presented in the discussion of domestic deposits in the chapter of Minerals Yearbook, 1941, on Molybdenum

and Vanadium.

Molybdenum contained in concentrates produced from Climax deposit in Colorado, 1918-42 1

Year	Pounds	Year	Pounds
1918-37 <sup>1</sup>	80, 060, 256 28, 242, 085 21, 796, 116 22, 782, 608	1941 1942 1918–42	27, 751, 273 41, 852, 136 222, 484, 474

<sup>&</sup>lt;sup>1</sup> For production by years, 1918-37, see chapter of this series for 1941. No production from 1920 to 1923, inclusive.

Molybdenite near Questa, Taos County, N. Mex., was first recognized during World War I. The deposit was developed by the R & S Molybdenum Mines Co., and about 100,000 pounds of molybdenum in concentrates were produced in 1919 and 1920. The Molybdenum Corporation of America acquired ownership in 1920 and built a mill and camp in 1923. Since that time the property has been in regular operation.

The mine is in Sulphur Gulch, 7 miles east of Questa; the mill is on Red River, three-quarters of a mile from the mine. The deposit covers an area about half a mile square, on the western flank of the Sangre de Cristo Range, at an elevation of 8,000 to 9,000 feet. Accord-

<sup>&</sup>lt;sup>1</sup> Vanderwilt, John W., The Occurrence and Production of Molybdenum: Colorado Sch. Mines Quarterly, vol. 37, No. 4, October 1942, p. 38. Structure of the Climax Molybdenite Deposit (in Ore Deposits as Related to Structural Features): Princeton Univ. Press, 1942, pp. 136-137.

ing to Vanderwilt,2 mineralization is in fissure veins near the contact of a small granite mass with a series of sedimentary and volcanic rocks. Numerous iron-stained fractures mark the mineralized area at the The deposit is unique in the production of large quantities of molybdenite from veins and is likewise outstanding in the richness of the ore (about 5 percent MoS<sub>2</sub>).

Mining and milling methods employed by the Molybdenum Cor-

poration of America at Questa have been described by Carman.3

Production of molybdenum in concentrates at Questa is summarized in the accompanying table.

Molubdenum contained in concentrates produced from Questa deposit in New Mexico, 1919-42

Year	Pounds	Year	Pounds	Year	Pounds	Year	Pounds
1919 1920 1921	65, 492 34, 900	1925 1926 1927	332, 293 334, 412 285, 833	1931 1932 1933	469, 800 515, 588 571, 500	1937 1938 1939	499, 182 438, 672 477, 327
1922 1923 1924	22, 667 140, 239	1928 1929 1930	450, 264 475, 925 639, 852	1934 1935 1936	571, 956 342, 000 405, 000	1940 1941 1942	484, 120 466, 856 376, 285

Molybdenite is present in all the important disseminated-copper deposits in southwestern United States and Mexico.4 Its recovery as a byproduct in the concentration of copper ores was begun in the United States by the Utah Copper Co. in 1936 from the Bingham deposit; it had already been accomplished in Mexico at Cananea in The Nevada Consolidated Copper Corporation became a molybdenum producer in 1937 from the Chino (Santa Rita) property in New Mexico, and in 1938 the Miami Copper Co. at Miami, Ariz., entered the field. These three producers supplied 24 percent of the 1942 production of molybdenum. The Bingham deposit is second only to Climax as a producer of molybdenum.

The molybdenum content of the various porphyry-copper deposits At Miami, the content is reported as 0.009 peris quite variable. cent MoS2; at Bingham 5 it is 0.04 percent; and at Chino the grade falls between these two.

Molybdenum is an accessory value at the Pine Creek tungsten mine of the United States Vanadium Corporation near Bishop, Inyo County, Calif. Lemmon<sup>6</sup>, discussing the deposit, states that the ores are mainly disseminated in contact-metamorphosed limestones. Molybdenite and powellite [Ca(Mo,W)O<sub>4</sub>] are the molybdenum minerals. The crude ore averages 0.5 percent MoO<sub>3</sub> and has a maximum of 2 percent MoO<sub>3</sub>. Burwell <sup>7</sup> has described the metallurgical

<sup>&</sup>lt;sup>2</sup> Vanderwilt, John W., Geology of the "Questa" Molybdenite Deposit, Taos County, N. Mex.: Proc. Colorado Sci. Soc., vol. 13, No. 11, 1938, pp. 599-643; see also reference in footnote 4, pp. 39-44. Molybdenite Mineralization near Questa, Taos County, N. Mex. (in Ore Deposits as Related to Structural Features): Princeton Univ. Press, 1942, pp. 245-246.

<sup>3</sup> Carman, J. B., Mining Methods of the Molybdenum Corporation of America at Questa, N. Mex.: Bureau of Mines Inf. Circ. 6514, 1931, 15 pp. Milling Methods at the Questa Concentrator of the Molybdenum Corporation of America, Questa, N. Mex.: Bureau of Mines Inf. Circ. 6551, 1932, 14 pp.

<sup>4</sup> Vanderwilt, John W., The Occurrence and Production of Molybdenum: Colorado Sch. Mines Quarterly, vol. 37, No. 4, October 1942, pp. 48 and 60.

<sup>5</sup> Vanderwilt, John W., Work cited in footnote 4, p. 60.

<sup>6</sup> Lemmon, D. M., Tungsten Deposits in the Sierra Nevada near Bishop, Calif.—A Preliminary Report: Geol. Survey Bull. 931-E, 1941, pp. 39-91.

<sup>7</sup> Burwell, Blair, Milling Tungsten Ores at Pine Creek: Min. Cong. Jour., vol. 27, No. 10, October 1941, pp. 16-18.

The Marie Commence of the Comm

problems in treating the ores, and Partridge 8 has given a brief history

of the property.

At Tiger, Ariz., Mammoth-St. Anthony, Ltd., carries on a unique operation involving the only commercial production of molybdenum from wulfenite (PbMoO4) in the United States. The molybdenum is in a complex ore which also carries values in gold, silver, lead, and The recovery process employed is described as follows in a communication from J. L. Fozard, general manager, Mammoth-St. Anthony, Ltd. (slightly abridged):

Smelting in a reverberatory furnace of oxide concentrates (which have been mixed with soda ash and coke) yields a lead bullion containing the bulk of the gold and silver; a small amount of matte carrying lead, copper, gold, and silver;

and a molybdenum-vanadium rich slag, which is treated at the plant.

The slag is hand-sledged, crushed, and ground wet in a rod mill. This solution contains the bulk of the vanadium and molybdenum that was in the slag. After suitable filtering, part of the solution is evaporated by smelter waste heat to the dry sodium molybdate-sodium vanadate salt; the remainder of the solu-

tion is used in the separation of the molybdenum from the vanadium.

In the salt plant, the currently made salt, stored salt, and salt solution are mixed, the amount of stored salt to be used being determined from the specific gravity of the solution. This mixture is agitated for 8 hours. The molybdenum gravity of the solution. This mixture is agitated for 8 hours. gravity of the solution. In mixture is agitated for a nours. The motyodenum of the solid salt goes into solution, and the vanadium of the solution is precipitated. The product is filtered, the residue being the vanadium shipping product, which assays 20-25 percent V<sub>2</sub>O<sub>5</sub> and less than 2 percent MoO<sub>3</sub>. The filtrate is then agitated with lime and calcium chloride for 2 hours. This material is filtered. The residue is a low-grade molybdate-silicate precipitate, which is stored for future re-treatment. The filtrate is treated with calcium chloride, and which grade calcium molybdate is precipitated filtered dried scaled and a high-grade calcium molybdate is precipitated, filtered, dried, sacked, and shipped.

EXPLORATION AND DEVELOPMENT

In 1942 the Defense Plant Corporation purchased the Urad mine, 10 miles from Empire in Clear Creek County, Colo., from the Vanadium Corporation of America. The Government agency was reported to have expended \$110,000 in the purchase and to have authorized the further expenditure of \$250,000 for development of the property by the Molybdenum Corporation of America, designated as operators. Production is scheduled to begin sometime in 1943. The Urad mine was a producer during World War I, having shipped several hundred thousand pounds of molybdenite concentrates in 1918 and 1919. Operations were suspended in 1919, and the mill was dismantled by the Vanadium Corporation of America, which acquired the property from the Primos Chemical Co.

No molybdenum has been mined commercially in Alaska, according to P. S. Smith, who summarized details on geology, mineralogy, and exploration of 41 occurrences of molybdenum minerals scattered through that Territory. Field work was performed on the Muir Inlet molybdenum deposit by the Geological Survey, and exploratory investigations were carried on by the Bureau of Mines; the latter agency also examined the Shakan deposit, Prince of Wales Island.

# CONSUMPTION AND USES

Since July 1941 the Bureau of Mines has conducted for the War Production Board (and its predecessor, Office of Production Management) monthly studies of production and consumption of molybdenum

Partridge, John F., Jr., Tungsten Resources of California: California Jour. Mines and Geol., vol. 37, No. 2, April 1941, pp. 295-296.

Smith, P. S., Occurrences of Molybdenum Minerals in Alaska: Geol. Surv. Bull. 926-C 1942, pp. 161-

and molvbdenum products. Responses from consumers of molybdenum products indicate that, of the total consumption (exclusive of scrap) of over 22,000 short tons of molybdenum in 1942, approximately 63 percent was consumed as molybdenum oxide (roasted molybdenite), 24 percent as ferromolybdenum, 12 percent as calcium molybdate, and the remaining 1 percent as metal or as one of the molybdenum chemicals. Monthly consumption of molybdenum in primary products increased from about 1,300 tons in January 1942 to 2,200 tons in December. Ninety-five percent of all the molybdenum (including scrap) was used in the production of steel ingots and castings, 3 percent in iron castings, and 2 percent in minor uses such as

pigments and colors, welding rods, etc.

An important step toward stretching available supplies of molybdenum and other critical steel-alloying metals was taken through adoption of specifications for NE (National Emergency) steels to replace the standard (SAE) steels. These alternate steels effect savings of critical metals through employment of leaner mixtures. The first specifications announced by the War Production Board in March 1942 included the Mn-Mo, Ni-Cr-Mo, and C-Mo steels. Revisions were made subsequently to meet changing conditions in supply of the metals involved. All but two of the compositions employing more than a maximum of 0.25 percent Mo were deleted.<sup>10</sup> Special attention was devoted to combining recoverable Ni, Cr, and Mo from scrap with small quantities of virgin metals, which led to introduction of two series containing 0.08 to 0.15 and 0.15 to 0.25 percent Mo, respectively.11

# IMPORTS AND EXPORTS 12

Molybdenum ore and concentrates were imported during 1941 and 1942. Total imports in 1942 amounted to 755,950 pounds (molybdenum contained), valued at \$554,232, compared with only 4,300 pounds in 1941 (value \$2,898). Molybdenum in other forms has not been imported since 1939, when 26,347 pounds contained in ferromolybdenum were received in the United States.

Molybdenum	ore	and	concentrates	exported	from	the	United	States,	1941-42,	by
The second second				countries	8 1					

		1941			1942		
Country	Pounds			Pounds			
	Gross weight	Molybde- num content	Value	Gross weight	Molybde- num content	Value	
Canada	974, 321 30, 255	500, 402 15, 000	\$400, 706 12, 000	1, 939, 801	1,027,372	\$816, 280	
U. S. S. R. United Kingdom	4, 715, 284 9, 625, 391	2, 367, 492 4, 757, 436	1, 777, 185 3, 189, 476	10, 339, 064 9, 182, 495	6, 107, 213 4, 482, 932	3, 960, 079 3, 182, 303	
	15, 345, 251	7, 640, 330	5, 379, 367	21, 461, 360	11, 617, 517	7, 958, 662	

<sup>&</sup>lt;sup>1</sup> Information from exporters indicates that figures from Department of Commerce may include molybdenum oxide or other compounds.

<sup>&</sup>lt;sup>10</sup> Roush, R. W., NE Alloy Steels: Steel, vol. 112, No. 9, March 1, 1943, pp. 94, 96, 98, 135-137.

<sup>11</sup> The development of NE steels and their properties are discussed in considerable detail in Steel, beginning with the issue of February 9, 1942.

<sup>12</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

A STATE AND AND ASSESSED AND ASSESSED ASSESSED.

# WORLD PRODUCTION

Canada.—Most of the molybdenum produced in Canada during 1942 came from Quebec, but small amounts were also obtained from

British Columbia and Ontario.

The Moss mine <sup>13</sup> of the Quyon Molybdenite Co. is in Onslow Township (Pontiac District), Que., about 33 miles west of Ottawa. The molybdenite is disseminated, generally as small flakes, through a granitic mass. From 1916 to early 1919, concentrates containing 765,091 pounds of MoS<sub>2</sub> were produced, and the property was the world's leading individual molybdenite producer. In 1938 development was revived. Ore reserves were estimated at 30,000 tons containing 0.53 percent MoS<sub>2</sub> in 1941. A 150-ton mill and smelter were built in that year, and roasted molybdenite (molybdenum oxide) briquets are the shipping product.

Siscoe Metals, Ltd., took over operation of a property in La Corne Township (Abitibi District), near Amos, Que., for the Wartime Metals Corporation, a Canadian Government agency. The mine was dewatered to the 250-foot level, and a 150-ton mill was started. The ore is reported to grade somewhat less than 0.5 percent MoS<sub>2</sub>,

and reserves were given as 40,000 tons in old reports.

In Preissac Township (Abitibi District), about 400 miles northwest of Quebec City, the Dome Exploration Co., located a molybdenite deposit in an area in which unsuccessful efforts were made during World War I to develop commercial ore bodies. Eardley-Wilmot, <sup>14</sup> describing the deposits in this area, states that they are mostly fissure-vein types. Drilling in 1942 indicated an ore zone at least 400 feet long and 200 feet wide, with an average width of 30 feet. The grade ranges from 0.245 to 1.188 percent Mo, and the average is approximately 0.92 percent. The company was awarded a substantial contract by the Canadian Government and at the end of 1942 was proceeding with construction of roads, camps, and a Production is considered a likelihood by the spring 500-ton mill. or summer of 1943.

The Phoenix property of the Zenith Molybdenite Corporation, Ltd., in Bagot Township, Renfrew County, Ont., is to be operated by the Wartime Metals Corporation. A small production was realized from this property during World War I. The mill will be rehabilitated and operated as a custom plant for the district.

Other molybdenum deposits, too numerous to mention, in Quebec,

Ontario, and British Columbia were under investigation.

French Morocco.—The Azegour molybdenite deposit, 15 50 miles southwest of Marrakech, in western Morocco, was first noted about 20 years ago. Small shipments were made in 1929, 1930, and 1932. A 100-ton mill was erected by the Société Le Molybdène in 1933. The mill heads were stated to average 1.08 percent MoS<sub>2</sub> and 0.05 In 1941, von der Weid 16 published a monograph on percent Cu. the deposit.

Azegour is unusual in being one of the few contact metamorphic

<sup>12</sup> Eardley-Wilmot, V. L., Molybdenum: Canada Mines Branch Rept. 592, 1925, pp. 150-155.
Chubb, W. F., Molybdenum Production in Canada: Metal Ind. (London), vol. 60, No. 14, April 3, 1942, pp. 236-237.
Wilson, M. E., Numerous Deposits of Molybdenite Known: Northern Miner, vol. 28, No. 14, June 25, 1942, pp. 32 and 39.

14 Eardley-Wilmot, V. L., Work cited in footnote 13, pp. 125-131.

15 Described in Bureau of Mines Minerals Yearbook, 1934, p. 433.

16 von der Weid, F., Le gisement de molybdenite d'Azegour et la région des Guedmioua (Atlas de Marrakech, Maroe): Librairie de l'Université, Geneva, 1941, 88 pp.

molybdenite deposits in which there are commercial quantities of ore. The molybdenite occurs almost exclusively in garnetized limestones near the contact with granitic intrusions. The ore mineral is local-

ized in interstices of the garnet rocks and in fractures.

According to statistics given by von der Weid the concentrates shipped from 1932 to 1938, inclusive, averaged 82.4 percent MoS<sub>2</sub>, and the total content of molybdenum was 516.5 metric tons. It was reported in the press that in 1939 the output was about 250,000 pounds of molybdenum. "Small amounts" were said to have been

exported in 1942.17

Manchuria.—Discovery of molybdenum at the Yangchiachantze properties of the Manchuria Lead Mining Co. in Chinchow Province was reported in 1939. The deposit was described as having a vein "several yards wide and about 100 yards long," with a metal content of 0.5 percent. In 1942 there appeared a news item 18 to the effect that as a result of intensified exploitation of the molybdenum deposits at Mienchiatzu and operation of a large "ore preparing and refining plant" the company was providing "equivalent to one-tenth the world's production" and hoped soon to be second to Climax.

Norway. For some years before 1934, Norway was the secondlargest molybdenum producer in the world. Since then, as far as available official statistics show, Mexico has occupied this rank. However, it was claimed recently that "Norway's production \* \* in 1940 was 900 tons (fine)." This figure indicates that in 1940 Nor-

way again ranked second.

The Knaben deposits, 40 miles east of Stavanger, are the principal sources of production. Molybdenite occurs in veins and disseminated in granitic rocks in a zone several kilometers long and a few hundred The ore mined in 1940 averaged 0.2 percent MoS<sub>2</sub>, meters wide. according to Quittkat,20 who described the milling process.

Early in March 1943 it was reported than an R. A. F. attack on the Knaben mill had damaged, and probably destroyed, the whole plant.21

World production of molybdenum in ores and concentrates, 1938-42, by countries, in metric tons

[Compiled by B. B. Waldbauer]

Country	1938	1939	1940	1941	1942
Australia <sup>1</sup> Canada <sup>1</sup> Chile Mexico Morocco, French (exports) Norway Peru Turkey United States	32 3 483 94 462 85 41 15,103	39 (2) 30 523 (4) 433 167 (4) 13,755	20 5 267 310 (4) (4) (9) 190 (4) 15, 564	10 46 229 522 (4) (4) 148 (4) 18, 217	8 36 8614 855 (4) (4) 219 (4) 25,890
Other countries 6	7 16,310	7 15, 100	7 17, 100	7 19, 800	7 28, 200

<sup>1</sup> Gross weight of ore and concentrates reported; molybdenum content estimated by authors.

3 10 months. 4 Estimate included in total.

Less than 1 ton.

<sup>&</sup>lt;sup>8</sup> Preliminary figure.
<sup>6</sup> Estimate for Greece, Italy, Rumania, and Yugoslavia included in total; in addition, molybdenum ore is produced in Burma, China, Chosen, Finland, Japan, Manchuria, and U. S. S. R., but data of productions of the production of the control o tion are not available.
7 Partly estimated.

<sup>17</sup> Foreign Commerce Weekly, Mining in French Morocco: Vol. 10, No. 11, March 13, 1943, p. 29.

18 Metal Bulletin (London), No. 2716, August 11, 1942, p. 12.

19 Metal Bulletin (London), No. 2774, March 5, 1943, p. 16.

29 Quittkat, G., Recovery and Dressing of Molybdenum Ores of the Knaben Mine, Norway: Metall u. Erz, vol. 38, 1941, pp. 261–264; Chem. Abs., vol. 36, 1942, p. 3758

21 Mining Journal (London), vol. 220, No. 5611, March 6, 1943 p. 120.

# **VANADIUM**

By Frederick Betz, Jr., and Alice P. van Siclen

#### SUMMARY OUTLINE

	Page		Page
Summary	665	United States—Continued.	_
War regulations	666	Exploration and development	668
Market and uses	666	Imports and exports	669
United States	666	World production and developments	670
Production in 1049	666		

## SUMMARY

World production of vanadium ores is limited almost entirely to four countries-United States, Peru, Northern Rhodesia, and South-West Africa. The United States displaced Peru as the leading producer in 1941 and increased its lead in 1942 to supply over 50 percent of the total world output. All important sources of vanadium ore are controlled by the United Nations. However, vanadium is also recovered as a byproduct from other ores and raw materials. Significant among the other sources are certain iron ores and crude The Axis countries apparently must rely on such sources, especially iron ores, and Germany is said to fulfill its requirements for vanadium in this manner. In the United States, vanadium ores have been supplemented with phosphate rock and imported vanadiumbearing flue dust to meet increased wartime needs. Titaniferous magnetite may yield future additions, and greatly increased exploitation of phosphate rock for its vanadium content is imminent.

Domestic shipments of vanadium ore in 1942 surpassed the record established in 1941 by 77 percent. More than 90 percent of the out-

put comes from the Colorado-Utah region.

Salient statistics of the vanadium industry in the United States, 1940-42

	1940	1941	1942
Ores and concentrates (vanadium contained):  Mine shipments	2, 162, 916 \$1, 044, 100 1, 548, 133 1, 204, 102 \$2, 350, 500 22, 551 \$1, 216, 705 (1) (4) (5) (6)	1 2, 513, 051 1 \$1, 179, 500 1, 853, 655 2, 052, 886 \$3, 968, 800 12, 323 2, 138, 608 \$1, 012, 991 25, 462 \$63, 213	4, 439, 130 \$2, 468, 100 2, 655, 784 2, 508, 632 \$4, 890, 800 18, 246 2, 422, 376 \$1, 274, 483 7, 22, 140 \$86, 218 154, 028 \$20, 645

Estimate by Bureau of Mines.
 Vanadium oxide (termed fused vanadium oxide, red cake, sodium vanadate) from domestic ores only.
 Data not available.

Not recorded.

## WAR REGULATIONS

The War Production Board placed Avanadium deliveries under allocation on December 20, 1941 (Order M-23-a). Melting of vanadium was made subject to approval of the melter's schedule in an amendment to Order M-23-a on June 23, 1942. This amendment also lowered the limit of unrestricted deliveries of vanadium from 50 to 10 pounds per month. A further amendment, issued December 26, defined vanadium as including ores and concentrates, primary vanadium compounds vanadium alloys, and waste products such as flue dust); ferrovanadium producers are exempt from melting restrictions and may freely acquire vanadium-bearing raw material; no authorization is required for melting 10 pounds of vanadium or less per month.

MARKET AND USES

The nominal price of 27% cents per pound of V<sub>2</sub>O<sub>5</sub> contained has been quoted for variadium ore since early in 1925, but there is a market by grades among mill operators. The average value of shipments, estimated from data collected by the Bureau of Mines, was 31 cents per pound in 1942, and prices as high as 50 cents were reported in sales to Metals Reserve Co, agencies, Vanadium pentoxide (technical grade) was priced at \$1.10 per pound of V<sub>2</sub>O<sub>5</sub> contained, and lerrovanadium was sold for \$2.70 to \$2.90 per pound of V contained. tained.

tained the property of the product is consumed as a second part of the product of Mines estimates that over 80 percent of the vanadium consumed is in the form of ferrovanadium. Figures of the War Production Board indicate that more than 60 percent of the total vanadium consumption is in tool steel, whereas nonmetallurgical uses absorb only 1 to 2 percent.

# UNITED STATES AND mathematic construction bus son

616 201 2

#### 1 644, 166 PRODUCTION IN 1942(houlding multislier) standoug line

zarsacjale ozilei Valev

The center of domestic vanadium-ore mining is in the Colorado-Utah region. A small output is realized in Arizona and Nevada, and vanadium-bearing phosphate rock is mined in Idaho to Producthon seems assured in the near future from the phosphate rock deposits in Wyoming, and recovery of vanadium from magnetite concentrates produced in New York is a possibility. Vacuadium-จังละวัน มีบิง ภิษย์:

The Colorado-Utah vanadium-ore region is an area comprising southwestern Colorado, southeastern Utah, and extending into northern Arizona. In recent years production has been limited to only a small part of the vanadium-ore region. Burwell 2 states that

Alexander, J., Vanadium and Some of its Industrial Applications: Chem. and Industrial Applications: Chem. and Industrial Applications of the Industrial App 871-878; 895-901.

Burwell, Blair, Vanadium Output Indicates Vigorous Progress: Min. Cong. Jour., vol. 29, No. 2, February 1943, pp. 27-29.

\*

and the same of th

during 1942, the principal producers, in cooperation with Government agencies, prepared for the development of jother, areas, by building roads (of which 300, miles were campleted), by opening ore-purchasing depots to provide a market for small producers, and by establishing plants mean the newly opened areas, to treat, ore from hitherto up touched and former marginal deposits, if The principal problem in ming is the interpretation of lore structures and, corollary thereto the following of the irregular course of the deposits of amount of the results at Rifle, and Placerville. Colomere found in the Entrada sandstoner According to Ticketer: 3

and he social entering the interior of the int

The principal vanadium mineralis mineraceous, and it has heretofore been thought to be roscoelite, the vanadium mica; but, as a result of recent X-ray studies to be roscoelite, the vanadium mica; but, as a result of recent X-ray studies to the visit of the vanadium perfectly understood hydrous mica forms group, of clay minerals to the vanadium bearing hydrous mica forms an aggregate of minute flakes, coating the sand grains. The whole was more strongly mineralized, the pore spaces are competerly filled with the dahadium mineral. This mineral imparts to the sandstone a gray or many shores. greenish-gravicolov which darkens as the vanadium content increases. be rever of The oder dottle for especial mined principally for their dranium and radium content from 1911 to 1923, but some vanadium was recovered as to byproduct from 1915 to 1923. With this advent of other bources of radiation moving of these ores was greatly curtailed. Since 1937 the word iction has been resumed on a larger scale, now primarily for the vanadium contentuir The Proscoelite ores were mined from 1909 to 1923 and 1925 to 1932 and since 1941. It is enoting its or is stigni hoppindipal producers in 1942 were the United States Vahadium Corporation, which operates mills at Uravan and Rifle, Colo, and la the operator for the Metals Reserve Color a mill at Durango, Cold, and the Vanadium Corporation of America, with a mill at Naturita, Colo., and one operated for the Metals Reserve Co. lat Monticello. Utalis The Raffe, Durango, and Monticello mills began producing vanadium bxide during 1942 tal Orest weller also milled by North Continebro Mines, Inc.; at Cedar, Colo; the Nisley & Wilson Vanadium Will at Cateway, Colo; and the Blanding Wines Co., Blanding, Utahr with Arriona wanddirm is recovered as sodium variadate from complex (gold-silver-lead-molybdenium-vanadium) ore by Mammoth-Stank then by Deal, at Piger, Pinal County, "The vanadium ore minerals are variadinite and descloizite. The process employed in recovering calclum malybeate and sodium vanddate is described in the chapter of regular fine-grained masses of mixed thamitsbdyloMigresiturby sills his 100 1923 the Ansonda Copper Mining Co. has mined phosphate rock at Conda, Caribou County Idaho. The rock, which is said to repairerung runt at which the heading Mithet Professe Mark 1444 & A. (DAID). A GRADA A GO STATE OF THE COLLEGE OF THE PROPERTY AND A COLDER CO

contain 0.3 percent V<sub>2</sub>O<sub>5</sub> (or about 0.16 percent V),<sup>5</sup> is treated at the Anaconda reduction works in Montana for the manufacture of superphosphate. It was not until 1941 that a byproduct recovery of the vanadium in the form of "red cake" (vanadium oxide containing approximately 90 percent V2O5) was effected. The fundamental recovery process was evolved by the A. R. Maas Chemical Co. and patented in 1935, according to F. C. Bowman of that company, who states that "The Anaconda Copper Company adopted the process and after considerable developmental research put it into commercial operation in 1941." The process in use now is summarized briefly as follows:7

The rock is treated with sulphuric acid, primarily for the purpose of leaching out the phosphoric acid. At the same time, approximately 65 percent of the vanadium contained in the rock goes into solution together with the phosphoric acid. This is precipitated as phospho-vanadic acid by treating the solution with sodium chlorate. The yellow crystalline precipitate is separated by settlement. It contains phosphorus, iron, alumina, lime, and other impurities. By treatment with milk of lime and sode ash under carefully controlled conditions the

ment with milk of lime and soda ash under carefully controlled conditions, the vanadium is obtained in a substantially pure sodium vanadate solution, from which vanadium pentoxide,  $V_2O_5$ , is precipitated by the addition of sulphuric

#### EXPLORATION AND DEVELOPMENT

The vanadium resources in phosphate rock are attaining greater potential significance. The Federal Geological Survey announced in February 1943 that, as a result of studies begun in 1939, millions of tons of ore containing small percentages of vanadium had been discovered in southeastern Idaho and southwestern Wyoming in the same phosphate rock formation now mined at Conda, Idaho. particular achievement was the discovery of an extensive shale horizon in the Phosphoria formation carrying commercial quantities of vanadium in a very finely divided state. The Bureau of Mines participated in the exploratory work in the Sublette and Afton areas of Wyoming and the Paris-Bloomington area of Idaho during 1942 and is continuing its investigations in 1943. Research on the metallurgical treatment of the ore has also been carried on to determine the best method of extracting vanadium. The Metals Reserve Co. contracted with the Homestake Mining Co. to develop these vanadium deposits. The work is being done by the Wyodak Coal & Manufacturing Co., subsidiary of the Homestake company.

An interesting mining development during 1942, which may affect the vanadium supply of the United States, was the reopening of the Lake Sanford titaniferous magnetite deposits in the Adirondack region of New York by the National Lead Co. The project, known as the MacIntyre development, was undertaken to provide a new domestic source of titanium for the manufacture of pigments. The ores of this region have long been known to contain small percentages of vanadium,8 but no commercial recovery has been made to date. Hagar 9 describes the ore body at Lake Sanford as consisting of "irregular fine-grained masses of mixed ilmenite and magnetite distributed in an anorthosite country rock." The vanadium is contained

Engineering and Mining Journal, Vanadium from Phosphate Rock: Vol. 143, No. 10, October 1942, p. 61.
 Oil, Paint and Drug Reporter, Phosphate Vanadium: Vol. 142, No. 16, October 19, 1942, pp. 4 and 73.
 Work cited in footnote 5.

Work cited in loothote 5.

§ Kemp, J. F., The Titaniferous Iron Ores of the Adirondacks: Geol. Surv. 19th Ann. Rept., part III, 1897-98, pp. 377-422.

Walz, I., On the General Occurrence of Vanadium in American Magnetites: Am. Chemist, vol. 6, No. 12, June 1876, pp. 453-456.

§ Hagar, I. D., The MacIntyre Development—New Source of Titanium: Eng. and Min. Jour., vol. 143, No. 12, December 1942, pp. 47-49.

in the magnetite; the content is 0.35 percent.10 The plans call for mining about 4,500 short tons of ore daily, with a production of 900 tons of ilmenite concentrate and 1,800 tons of magnetite concentrate. The magnetite and ilmenite are associated in a mechanical mixture, according to Hagar, permitting ready separation of the ore minerals.

The recovery of vanadium from the Lake Sanford magnetite was the subject of an investigation by the Bureau of Mines, the National Lead Co., and the University of Minnesota.11 According to the

report on the investigation:

(p. 2) It appears that most of the vanadium in this ore can be recovered in pig iron, which can be blown in a converter to produce a slag containing vanadium in amounts suitable for the production of ferrovanadium.

(p. 23) A recovery in the metal of 87.3 percent of the vanadium was obtained during the operation of the experimental blast furnace on burdens composed of the conditions of the state of the conditions of the state of the conditions of the conditi iron ore and titaniferous sinter containing 11.1 percent TiO<sub>2</sub> and 0.26 percent vanadium. Approximately 4 percent of the vanadium was lost in the slag. These results show that the oxides of vanadium are reduced readily under blastfurnace conditions.

The potential annual recovery of vanadium from the Lake Sanford ore has been estimated at about 3,000,000 pounds in the form

of ferrovanadium.12

Wood, Joseph, and Cole 13 call attention to several recent foreign experiments on methods of recovering vanadium from iron ore and slags. A more extensive review of recent literature on vanadium recovery, emphasizing especially Russian and German metallurgical work on these sources of vanadium, was prepared during 1942 by Lathe <sup>14</sup> of the National Research Council of Canada.

# IMPORTS AND EXPORTS 15

In 1941 imports of vanadium ore and concentrates were obtained almost exclusively from Peru and totaled 24,645,686 pounds with a vanadium content of 2,138,608 pounds. Other sources, especially South-West Africa, augmented the supply of vanadium in 1942, as is shown in the following table.

Vanadium ore and concentrates and vanadium-bearing flue dust imported for consumption in the United States in 1942, by countries

	Ore	and concent	rates	Vanadium-bearing flue dust		
Country	Pou	ınds		Pou		
Country	Gross weight	Vanadium content	Value	Gross weight	Vanadium content	Value
Canada Curaçao (N. W. I.)	31, 610, 284	2, 053, 399	\$979,037	370, 217 125, 303 128, 903	73, 074 11, 818 69, 136	\$15, 554 9, 835 <b>4,</b> 156
South-West Africa 1	4, 881, 984 36, 492, 268	368, 977 2, 422, 376	295, 446 1, 274, 483	624, 423	154, 028	29, 54

<sup>1</sup> Reported by Department of Commerce as Union of South Africa.

<sup>10</sup> In 1922, F. L. Nason (The Importance of the Iron Ores of the Adirondack Region: Am. Iron and Steel Inst. Yearbook, 1922, New York, pp. 168-207) published a complete typical analysis of the Lake Sanford ore. The crude ore was reported to contain 0.35 percent V<sub>2</sub>O<sub>5</sub> (or 0.196 percent V), and the concentrates gave 0.47 percent V<sub>2</sub>O<sub>5</sub> (or 0.26 percent V).

11 Wood, C. E., Joseph, T. L., and Cole, S. S., Smelting of Vanadium-Bearing Titaniferous Sinter in an Experimental Blast Furnace: Bureau of Mines Rept. of Investigations 3679, 1943, 24 pp.

12 Mining and Contracting Review, MacIntyre Development—Historic Mine Reopened: Vol. 44, No. 13, July 15, 1942, pp. 7 and 17.

13 Wood, C. E., Joseph, T. L., and Cole, S. S., Work cited in footnote 11, pp. 3-5.

14 Lathe, F. E., Review of Recent Literature on Vanadium Recovery with Special Reference to Vanadium Iron Ore: Nat. Res. Council Canada, N. R. C. No. 1075, June 1942, 32 pp.

14 Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Salar Maria Carlo

A STATE OF

10 Alla exports of variadium ore and concentrates Militarz went to Canada of the total was 73,542 poulds (vanadim of the the 22,140 tons of the magnetite and ilmenite are associated in a mechanical initiation.

according terhamqolavadudnashorroudosquadagow minerals. The recovery of vanadium from the Lake Sanford magnetite was la Canada H Canada does not produce any vanadium ores of Accord ing to Bateman, 9 small amounts of wanadium are recovered from soot and ashes collected from oil-burning vessels of The Metal Controller's Office presented a schedule of prices for vanadium bearing petroleum soot ... The schedule is quoted as this source of vanadium has gained some importance recently in The prices in Canadian currency per point of contained V/0 in the prices in Canadian currency per point of contained V/0 in the prices in Castleton, N in it by grades follow: b. to 1, 10 percent, 1, 20 a. 43 cents; 8 to 10.9 percent, 46 cents 1.1 to 13.9 percent, 49 teents; 17 percent and more, 54 rcents Mix Bateman stated that open-hearth slags of the Dominion Iron & Steel Ob. at Sydney, Nova Scotia, contain enough vanadium (which he believes could be recovered) to meet Canadian vneeds vifonecessary. The slags H lare derived from Newfoundland (Wabana) livernores rused and Sydney Vanadium was found in titaniferous magnetites examined by the Ontario Department of Mines in Papineau Township Oht Jouring 1942 ro Grab samples assayed 0.63 to 0.99 percent ViOs 12 manages mi Germany :- Extensive research ton viecovery of wanadium from eiron lores has been reported from Germany la It is generally assumed that the vanadium supply is derived from this source but no spositive knowledge of the output is indicated in published reports. Plander ? states that German ores yield the greater part of that country's requirements of over 10,000 tons of variation annually, produced in the form of an iron-vanadium alloy by conversion of slag. The stated requirements are striking, as they exceed the entire world production of vanadium from ores and probably from all other raw materials; also, they represent a very marked increase over German consumption in earlier years. Zieler 21 reported that the consumption was estimated at about 150 metric tons of vanadium contained in ferrovanadium in 1924 and at 200 to 400 form in 1924. dium in 1934, and at 300 to 400 tons in 1937, and that a considerable increase was indicated in 1938; solut boting off in notiquing

Northern Rhodesia. Vanadium is the principal product, in terms of value, now recovered from the Broken Hill lead-zinc-vanadium deposit.22 The ores, occurring in a series of steeply dipping lenses replacing dolomite, are roughly zoned, the rich vanadium ores being developed largely in the broken ground between the massive oxidized ores and the dolomite, as well as in fissures. The vanadium ore

<sup>16</sup> Bateman, G. C., Canadian War, Metals Developments: Min. and Met. Soc. Bull. 267, vol. 36, 160, 1, January 1943, pp. 3-15. Also published under title, The Canadian Mining Industry in Wartime: Trans. Canadian Inst. Min. and Met., vol. 46, March 1943, pp. 71-79.

<sup>4,</sup> and 5.

18 Northern Miner, Vanadium Sought: Vol. 28, No. 32, October 28, 1942, p. 6.

19 Northern Miner, Titaniferous Iron Find Reported: Vol. 28, No. 36, November 26, 1942, p. 9.

20 Planner, Bernard, P., Emergency Production Methods Used by the German Tron and Steel Industry:

Min: and Met.; vol. 23, No. 429, September 1942, p. 466.

20 Zeler, Hans, Die Gewinntung von Vanadin aus deutschen Robstoffen: Stahl u. Eisen vol. 58, No. 28, July 14, 1938, pp. 749-756.

21 Denns, T., The Mineral Resources of Northern Rhodesia; Bull. Imp. Inst., vol. 40, No. 4, October-December 1942, pp. 295-306.

<sup>...</sup> ituis and containing access, adam intercongues to the politics of the poli

Ť,

The transfer of the second of

1.

1

1

minerals are descloizite and vanadinite. Vanadium-bearing laterite. in many places containing 3 percent V, is also mined at the surface. The export of vanadium ore was begun in 1921. Facilities for producing fused vanadium oxide were put into operation in 1930 in The ore treated in the vanadium plant averaged 1.41 percent V in 1939. Proved reserves in June 1940 at Broken Hill were 2,400,000 tons of exidized or containing 0.83 percent  $V_2O_5$  or approximately (11,200 tons) of variation. The Camernor variation deposit, 20 miles northeast of Broken Hill, has been worked on a small scale only and Peru, Peru, has been an important source of wanadium for many years, From 1988 to 1940, inclusive, and in several earlier years at was the largest producing country in the world. Principal source is the famed Mina Ragra of the Wanadium Corporation of America in the Andes near Rigran, Department of Junin, I The vanadium ore occurs associated with asphalt and was first prospected as a source of fuel for the Huaraucaca smelter, but because of the sulfur content the mine was abandoned. In 1905, Rizo Patron, the smelter manager, discovered that this carbonaceous material was rich in vanadium, and steps were taken immediately to explore the property. Patronite, the yanadium sulfide (named after its discoverer), was abundant in the deposit, but, is now virtually mined out. The remaining ore is largely a red calcium vanadate which carries up to 50 percent V2O5, occurring in pockets and filling cracks or fissures in the shales. The ore is surface-mined from an open pit 650 meters long and 360 meters wide, Operations at the reduction plant include reasting, lixiviation, precipitation, filtering, and drying. In the past, concentrates averaging 15 percent Vand ores including ashes averaging 4 to 5 percent Were experted but it is planned to ship only higher-grade concentrate or precipitate with about 50 percent V content, to reduce the volume of shipping space required as well as freight charges. During 1942 a new treatment plant, with a daily capacity of 200 tons of lower-grade ore was under construction, which, with the 80-ton plant already in operation, would permit doubling the output. Total ore reserves are estimated at somewhat less than 500,000 tons, consisting of 27 percent "vets madre" are with 4 percent V, 40 percent "broza" ore with 0.9 percent Vol and the remainder flotation and leached tailings and a small tonnage of oxide dumps averaging 0.7 percent. V. "The total manadium content of this ore is said to exceed 6,000 tons.23 A minor source of vanadium is the vanadiferous ashes derived from asphaltites; the largest deposits of this material are at Yauli, Department of Junin, where the asphaltite was used at one time as a coal substitute. The V2O5 content of the ash may be as high as 20 percent, but ordinarily it is much lower.24

South-West Africa. Vanadium deposits of distinctive character are numerous in the Ofavi Mountains of northern South-West Africa over a distance of some 60 miles between Uris and Berg Aukas.

Mineral Trade Notes, Bureau of Mines, Mineral Industries of Peru: Spec. Suppl., Confidential Series, No. 6, December 1942, pp. 12-13.

\*\* See also:

M See also:
Baragwanath, John G., The Vanadiferous Asphaltites of Central Peru. Eng. and Min Jour vol. 111,

Hess, Frank I., Vanadium: Bureau of Mines Inf. Circ. 6572, April 1982, pp. 4-5.

Hess, Frank I., Vanadium: Bureau of Mines Inf. Circ. 6572, April 1982, pp. 4-5.

Hewett, D. F., Vanadium Deposits in Peru: Am. Inst. Min. and Met. Eng., vol. 40, 1910, pp. 274-288.

4. Clark, A. W., The Ore Deposits of the Otavi Mountains, South-West Africa: Min. Mag., vol. 44, No. 5, May 1931, pp. 265-272.

pp.41-44. Stahl, A., Die Vanadinlagerstätten Afrikas, insbesondere S. W.-Afrikas: Metallwirtschaft, vol. 21, No. 19, May 15, 1942, pp. 297-299.

The first discovery was made at Tsumeb-West before World War I. After the war, search revealed many other occurrences, including that of Abenab in 1921, which proved to be one of the largest vanadium

deposits in the world.

The copper-lead-zinc vanadates of the Otavi region occur in a thick, folded series of dolomites and limestones. Cavities ("sandsacks") in the country rock are filled with lumps of vanadates (mainly descloizite and cuprodescloizite), blocks of silicified dolomite, and red The vanadates also encrust the dolomite blocks and dune sand. walls of the cavities and penetrate as veinlets into the adjacent country rock. Some of the "sandsacks" are the weathered outcrops of ore-bearing pipes or sink holes, but others show no ore below the cavities. The ore bodies are highly variable in size. The Abenab pipe deposit is 200 by 120 feet at the surface, but the Uris is only 50 to 60 feet across and the majority are considerably smaller.

crude ore contains 2 to 3 percent V<sub>2</sub>O<sub>5</sub>.

Abenab and another deposit operated by the Southwest Africa Co. are now producing 300 tons of concentrates (averaging 18 percent V<sub>2</sub>O<sub>5</sub>) a month. In earlier years this company produced also at Baltika, but the deposit was exhausted in 1939. The depletion of present reserves may be counteracted by further development work or discoveries. The Otavi Minen- und Eisenbahn-Gesellschaft formerly operated the Tsumeb and Uris deposits. The company suspended operations in September 1940. Subsequently it was reported that the South African Government would assume operation of the company properties. Shipments were made in 1942, and the production rate is reported as 40 to 60 tons per month of 10.5-percent V<sub>2</sub>O<sub>5</sub> The Karavatu deposit is apparently the source of concentrates. present output from the Otavi holdings.

The total output from South-West Africa since 1920 has been over 65,000 short tons of concentrates or more than 6,500 tons of

contained vanadium.

Venezuela.—The soot of Venezuelan oils, especially from Maracaibo, contains as much as 34 percent V<sub>2</sub>O<sub>5</sub>.26 During 1942 several thousand pounds of soot were shipped by oil companies, which obtain the product from smokestacks of their tankers and power plants.

World production of vanadium in ores and concentrates, 1938-42, in metric tons [Compiled by B. B. Waldbauer]

Country	1938	1939	1940	1941	1942
Argentina	101 374 826 557 732 2,590	15 83 384 996 514 900	1 32 (1) 1,214 428 981	(2) (1) 1,017 269 4 1,140	(1) 3 1,008 (1) 2,014 3 3,800

<sup>1</sup> Data not available; estimate included in total.

Less than 1 ton. 3 Preliminary figure; subject to revision.

<sup>26</sup> Iron and Coal Trades Review, The Ferro-Mineral Resources of South America: Vol. 145, No. 3892, October 2, 1942, pp. 889-892.

## TUNGSTEN

By H. W. DAVIS

#### SUMMARY OUTLINE

	Page		Page
Summary	673	Domestic production.	675
Salient statistics	673	Foreign trade	681
Government exploration	674	Consumption and uses	682
Prices	675	World production	682

#### SUMMARY

Stimulated by greatly increased needs for tungsten in the military program and by higher prices, production of tungsten concentrates and high-grade sorted ore in the United States, despite the shortage of labor at many mines, reached a new peak in 1942. The labor shortage was relieved somewhat when the Army released some soldiers for work in tungsten mines. Domestic production was 9,433 short tons (60 percent WO<sub>3</sub> basis) in 1942, or 40 percent more than in 1941, the previous record year. Virtually the entire gain was contributed by California, Idaho, and Nevada, as output in all other producing States (except Texas) declined. The combined production in California, Idaho, Nevada, and Texas increased 54 percent over 1941: that in the remaining producing States decreased 37 percent. operators—one each in California, Idaho, and Nevada—accounted for 70 percent of the total 1942 output. The Yellow Pine mine in Idaho. which made its initial production in 1941, rose to be the second-largest producer in the United States in 1942. Probably more prospecting and developing were done on domestic tungsten-ore deposits during 1942 than in any other single year. New mills were completed at several mines.

Salient statistics of tungsten ore and concentrates in the United States, 1941-42

	1941		1942	
	Shortitons, 60 percent WO <sub>3</sub>	Value	Short tons, 60 percent WO <sub>2</sub>	Value
Domestic production	6, 746 6, 567 13, 820 12, 107 2, 527	\$9, 223, 726 11, 231, 313 (1)	9, 433 9, 333 15, 851 14, 715 3, 590	\$13, 508, 266 (1) (1) (1)

<sup>1</sup> Figures not available.

Value

Notwithstanding shipping difficulties, receipts of imported ore and concentrates increased 15 percent over 1941 to an all-time high of 15,851 short tons (60 percent WO<sub>3</sub> basis) in 1942. Of the 1942 total, Argentina supplied 17 percent, Bolivia 43 percent, and China 30 percent.

Consumption of tungsten or land concentrates also reached a new peak in 1942 and amounted to 18,300 short tons (60 percent WO<sub>3</sub> basis), a gain of 5 percent over 1941. He was

To aid further in stimulating the domestic production of tungsten. the Metals Reserve Co. announced on April 22, 1942, that its domestic price policy of \$24 per dry short-ton unit of WO<sub>3</sub> would remain in effect until December 31, 1943. In November 1942 the price was increased to \$30 a unit about all the price was repeated in adomestic shipments, imports, and prices and applicable of the price shipments, imports, and prices of tungsten ore and concentrates since 1915.




FIGURE 1.—Trends in domestic shipments, imports, and average price of tungsten ore and concentrates, 1915–42.

1060 in 100 GOVERNMENT EXPLORATION

Continuing its search for strategic minerals, the Bureau of Mines investigated deposits of tungsten in Idaho, Colorado, Nevada, Wyo ming, New Mexico, and Alaska during 1942. Exploration was continued at the Ima mine in Lemhi County, Idaho, in the Boulder County (Colo.) field, and at the Riverside mine at Hyder, Alaska. substantial tonnage of low-grade ore was indicated by trenching and diamond drilling at the Tungstonia deposit in White Pine County, Surface trenching and diamond drilling on the properties of the North Tem Piute Mining & Development Co. and Tem Piute Mining Co. in Lincoln County, Nev., indicated a fairly large tonnage of low-

grade ore. At the property of the Tungsten Mining Consat Cherry Creek, White Pine County, Nev., five scheelite lenses were explored by trenching and diamond drilling that indicated a substantial tonnage of low-grade ore. In New Mexico, exploration works was done in the Iron Mountain tungsten deposits in Sierra County! In the West Tintic district, Utah, diamond drilling and underground in West cated that a small production of tungsten ores will be available. The Romur tungsten property in Fremont County, Wyo. In presents the possibility of opening up an entirely new tungsten-mining district. Exploration was begun on this property in November 1942. A limited program of trenching, sinking shallow shafts, and drifting underground by the Bureau has indicated that this district may contribute a large tonnage of tungsten.

The Geological Survey continued and expanded examination of domestic tungsten deposits as part of its program of the vestigations of strategic mineral deposits. Altogether, over 100 separate areas, including more than twice that number of individual deposits, were examined, many of them at the request of various other Government agencies. This work was distributed over all of the Western States, Alaska, and, in the latter part of the year, northern Mexico. Markan number of the more promising deposits were studied in detail some other districts previously examined were reviewed. In several districts, Survey geologists collaborated with the Bureau of Mines on exploration projects; among these were Boulder County, Colo.; Seven Devils, Idaho; Cherry Creek, Tempiute, and Tungstonia, News are win, Calif.; and Hyder, Alaska. Reports on earlier work at Silver Hill, Wash., and in the Nightingale district, Nev., were published in 1942.

PRICES

Quotations on tungsten ore and concentrates were steady throughout 1942. According to the Engineering and Mining Journal, Chinese, Bolivian, and Portuguese ore was quoted at \$24 a short-ton unit of WO<sub>3</sub>, duty paid, and domestic scheelite, in carlots, delivered, at \$26 a short-ton unit. The buying price of Metals Reserve Co. for domestic ore and concentrates from "eligible" producers was \$24 a short-ton unit until November 19, 1942, when it was increased to \$30. The average price for the domestic concentrates and high-grade sorted ore shipped in 1942, as reported to the Bureau of Mines, was \$24.42 a short-ton unit of WO<sub>3</sub>.

#### DOMESTIC PRODUCTION

Spurred by the need for tungsten to successfully prosecute the war, production of tungsten concentrates and high-grade sorted war, production of tungsten concentrates and high-grade sorted war, united States gained 40 percent over 1941 to reach an all times high of 9,433 short tons (reduced to an equivalent of 60 percent we high operations in Alaska, Arizona, California, Colorado, Idaho, Montanes, Nevada, Texas, Utah, and Washington. However, California, Idaho, and Nevada supplied 93 percent of the total output, and three coperators (one in each of these States) produced 70 percent of the United States total. California, which displaced Nevada as the principal producing State in 1940, maintained its rank in 1942.

In addition to the output of 9,433 tons of concentrates and high-grade sorted ore, a considerable tonnage of low-grade concentrates,

which require further milling, was produced in 1942; these concentrates have been or will be shipped to the re-treatment plant of Metals Reserve Co. at Salt Lake City, Utah, which was expected to begin operating in April 1943. The resultant high-grade concentrates recovered from this material will be included in later production and shipment figures.

Tungsten ore and concentrates produced and shipped in the United States, 1941-42, by States

		Prod	uced		Shipped from mines					
<b>.</b>	19	41	19	42	19	41	194	12		
State	Short tons, 60 percent WO <sub>3</sub>	Units	Short tons, 60 percent WO <sub>3</sub>	Units	Short tons, 60 percent WO <sub>3</sub>	Units	Short tons, 60 percent WO <sub>3</sub>	Units		
Alaska Arizona California Colorado Idaho Missouri	26 280 2,704 646 663 3	1, 590 16, 793 162, 229 38, 740 39, 781	(1) 209 3, 495 380 2, 132	(1) 12, 531 209, 702 22, 810 127, 934	277 2, 603 631 656	16, 602 156, 203 37, 839 39, 381 164	(1) 219 3,483 376 2,108	(1) 13, 141 208, 961 22, 574 126, 465		
Montana Nevada New Mexico South Dakota	7 2,316 } 3	415 138, 983 170	(1) 3, 135	(1) 188, 071	2, 289 3	415 137, 321 170	(1) 3, 052	(1) 183 <b>, 12</b> 6		
TexasUtah Washington Undistributed	30 68	1,802 4,103	(1) 30 45 7	(1) 1,786 2,695 428	30 68	1,806 4,103	(1) 29 43 23	(1) 1, 717 2, 590 1, 403		
	6, 746	404, 770	9, 433	565, 957	6, 567	394, 004	9, 333	559, 977		

<sup>&</sup>lt;sup>1</sup> Included under "Undistributed."

Tungsten ore and concentrates shipped from mines in the United States, 1938-42

	Quai	ntity	Reported value f. o. b. mines			
Year	Ore and concentrates, 60 percent WO; (short tons)	Tungsten content (pounds)	Total	Average per unit of WO <sub>3</sub>	Average per pound of tungsten	
1938 1939 1940 1941 1942	3, 044 4, 287 5, 319 6, 567 9, 333	2, 897, 036 4, 080, 024 5, 062, 199 6, 249, 945 8, 882, 403	\$3, 161, 498 4, 402, 182 6, 576, 318 9, 223, 726 13, 508, 266	\$17. 31 17. 11 20. 61 23. 41 24. 12	\$1.09 1.08 1.30 1.48 1.52	

Alaska.—At the Riverside mine near Hyder, virtually the entire 1942 operating season was devoted to treating slimes from previous operations, from which a small tonnage of concentrates was recovered and shipped. According to J. H. Scott, owner and operator of the mine, these slimes were difficult to treat, but toward the end of the season the metallurgical difficulties were solved. In the mill, 14 additional flotation cells and other equipment were installed. Some underground work was done in the mine, which brought about the discovery of good ore.

Arizona.—Production of tungsten concentrates in Arizona was 181 short tons averaging 69.23 percent WO<sub>3</sub> in 1942, compared with 251 tons averaging 66.90 percent WO<sub>3</sub> in 1941. Shipments were 192 tons averaging 68.44 percent in 1942 and 246 tons averaging 67.49

A CONTRACTOR OF THE PARTY OF TH

percent WO<sub>3</sub> in 1941. The output comprised scheelite, wolframite, huebnerite, and ferberite. By far the largest output came from the Boriana mine near Yucca, Mohave County, where wolframite and scheelite concentrates averaging 68.74 percent WO<sub>3</sub> were recovered from milling a 1.05-percent WO<sub>3</sub> ore in 1942. The mining and milling of tungsten ores at the Boriana mine were described recently by Munds.<sup>1</sup> The remainder of the output, which was produced at a number of widely scattered operations, came chiefly from the Tungsten Reef mines in Cochise County, Chloriding and Diff claims in Mohave County, and Morning Star claim in Pinal County.

California.—California maintained its rank as the principal tungsten-producing State in 1942. Shipments of tungsten concentrates (virtually all scheelite) from California totaled 3,334 short tons averaging 62.68 percent WO<sub>3</sub> in 1942, compared with 2,629 tons averaging 59.42 percent WO<sub>3</sub> in 1941. Although tungsten concentrates were shipped from a large number of widely scattered operations, six producers—the Atolia Mining Co. (in San Bernardino County), and the United States Vanadium Corporation, Tungstar Corporation, West Coast Tungsten Co., El Diablo Mining Co., and Bishop Tungsten Corporation (all in Inyo County)—accounted for 3,051 tons, or 92 percent of the State total. The bulk of the remainder was shipped from the Garnet Dike mine in Fresno County; Tungsten City and Victory mines in Inyo County; Stardust and Tungsten Chief mines in Kern County; Quigley mine in Madera County; and Big Jim, Dinuba, and Posey mines in Tulare County.

Production of tungsten concentrates in California was 3,324 short tons averaging 63 percent WO<sub>3</sub> in 1942, compared with 2,747 tons averaging 59 percent WO<sub>3</sub> in 1941. Of the 1942 total, Invo County supplied 79.9 percent; San Bernardino 14.2 percent; Tulare 1.1 percent; Kern 1.0 percent; and Fresno, Mono, Madera, and Tuolumne Counties together 1.4 percent; the source of 2.4 percent was not reported. The largest producer in California, as well as in the United States, during 1942 was the United States Vanadium Corporation, which operated the Pine Creek mine near Bishop and, in addition, milled ore and tailings from other properties in California and in Nevada; the concentrates recovered from milling ore and tailings from Nevada have been credited in the statistics to that State. The new 1,300-ton concentrating and chemical plant of the company was put into operation the latter part of 1941, and as a consequence production of concentrates increased 77 percent in 1942 over 1941. The milling plant has been described by Burwell.<sup>2</sup> Development done in 1942 at the mine included 16,954 feet of diamond drilling, 2,677 feet of raises, 1,082 feet of crosscuts, and 2,926 feet of drifts. Mine development at the close of 1942 comprised adits and tunnels with sublevels and raises connecting approximately 12,000 feet in main levels and 8,000 feet in sublevels.

The Tungstar Corporation, operating the Tungstar mine near Bishop, completed at a cost of \$135,000 a new aerial tramway, having an inclined length of 11,800 feet and a capacity of 100 tons in 8 hours, to transport ore from the mine to the mill. The tramway has been described by Engineering and Mining Journal.<sup>3</sup> The company also

<sup>1</sup> Munds, W. H., Mining and Milling Tungsten Ores at Boriana: Min. Cong. Jour., vol. 28, No. 9, September 1942, pp. 14-16.
2 Burwell, Blair, Milling Tungsten Ores at Pine Creek: Min. Cong. Jour., vol. 27, No. 10, October 1941,

pp. 16-18.
Engineering and Mining Journal, vol. 143, No. 9, September 1942, pp. 64-65.

did 1300 feet) of standeling and drifting into an ore body containing about 50,000 tons of ore averaging 0.75 to 1 percent WO<sub>3</sub>. Work was barried on by sinking below tunnel level of the original ore body, where about 20,000 tons of 1.5- to 2-percent WO<sub>3</sub> ore were developed. This company operated its mill on a one-shift basis for 9 months but was idle 3 months because of its inability to transport ore from the mitter become quently production of concentrates declined markedly in 1942. That monty the ideas

The Adamson mine rear Bishop was being developed by Panaminas (Inc.) in 1942. A plant was under construction, two adits were started at the 13300-160 tilevely and a jib-back tram to the upper ore bodies was

of tungsteibeligeningd

California, and several new mills were completed, but lack of space

predudes giving detailed information.

Colorado. La Production of tungsten concentrates in Colorado dedirect to 492 short tons averaging 46 percent WO<sub>3</sub> in 1942 from 810 tens averaging 48 percent WO<sub>3</sub> in 1941, and shipments dropped to 491 from 787 tons a Virtually the entire ouptut was ferberite from Boulder County, the greater part of which came from operations of the Wolf Trongue Mining Country and the Vanadium Corporation of America. The bulk of the transinder came from operations of George H. Teal & Associates S. W. Shattuck Chemical Co., W. L. & S. H. Tanner, Tom Whish, and Boulder Tungsten Mills (Inc.). Most of the concentrates produced by George H. Teal & Associates and Boulder Tungsten Mills were shipped to the re-treatment plant at Salt Lake City, Utah, for further trailing. A comparatively small quantity of huebnerite was produced in 1942 in San Juan County and a little ferberite in Summit County!

suffice and underground), surface trenching, drifting, and crosscutting but found into additional ore bodies. Core drilling was done at the Derothy mime of George H. Teal & Associates, and two ore bodies were found to have commercial value. At the Pueblo Belle mine of the S. W. Shattuck Chemical Co. the shaft was sunk from 160 to 360 feet, but no ore was found below the 320-foot level; at the 200-foot level the drift was being extended eastward. Boulder Tungsten Mills (Inc.) completed a mill in mid-1942, which treated ore from its own mines and purchased ore; the company began unwatering and

retimbering eight mines.

phenomenally to 2 389 short tons averaging 53.55 percent WO<sub>3</sub> in 1942 from 1,291 tons averaging 30.81 percent in 1941. Shipments of higheracle concentrates were 2,366 tons averaging 53.45 percent in 1942, compared with 1,269 tons averaging 31.03 percent WO<sub>3</sub> in 1941. In addition, 7,023 tons of low-grade flotation concentrates averaging 10.56 percent WO<sub>3</sub> were produced in 1942, of which 5,984 tons averaging 10.56 percent WO<sub>3</sub> were shipped to the re-treatment plant at Salt Lake Oity, Utah, for further milling. These low-grade concentrates have been omitted from the 1942 statistics, but the resultant high-grade concentrates recovered will be included in later figures.

The chief tungsten-producing mine in Idaho and second-largest in the United States was the Yellow Pine near Stibnite, in Valley County, where tungsten production was begun by the Bradley Mining Co. in August 1941. In 1942 this mine produced and treated 96,861

, X

1

j.

short tons of scheelite ore averaging 2,61 percent WO, which yielded 2,276 tons of high-grade concentrates (52.98 percent WOs) and 6,905 tons of low-grade concentrates (10.48 percent WO3) Most of the low-grade concentrates were shipped to the re-treatment plant at Salt Lake City for further milling an About four fifths of the output in 1942 came from underground workings. () During 1942 two Hardings ball mills (making a total of 4), additional flotation cells (making a total of 12)) and auxiliary equipment were installed; as a result, production in 1943 is expected to be double that in 1942 although the grade of ore will be lower dy In 1943 at least three fifths of the output will be from open pit operations to The Yellow Pine mine has been described recently by Bradley, Mecia, and Baker 1 at 1 and 1 Production at the Ima/mine in the Blue Wing district, Lembi County, was 36 percent less than in 1941 Methods and costs of concentrating huebnerite ores at the Ima mine have been described been under development for some time, made its initial design vid ha Tungsten became an important product of the Atlanta Group of claims near Atlanta, Elmore County, in 1942, These claims, operated by Talache Mines (Inc.) are Idaho's chief gold producers, and exploration has revealed tungsten ore in commercial quantities; however, the ore is of low grade in tungsten and could not be mined without its gold and silver content to supplement its tungsten value. One section bf-the company mill was converted to treat tungsten ore during 1942; 13,675 Short tons of schedite ore averaging 0.15 percent WO were produced and treated, yielding 118 tons of concentrates averaging 12.26 percent WO3, most of which were shipped to the restreatment plant at Salt Lake City for further milling. stisogeb netsgant edT

Montana.—Small quantities of scheeliten were a recovered from a waste dump in Park County and as a byproduct of placer mining in Rowell County in 1942. It is sould a sea by a superior of the placer mining in Rowell County in 1942. It is sould a sea by a superior of the sea o

Nevada.—Nevada maintained its rank as the second-largest tungsten-producing State in 1942. Production and shipments of concentrates (reduced to an equivalent of 60 percent WO<sub>3</sub>) were 3,185, and 3,052 short tons; respectively, compared with 2,316, and 2,289 tons, respectively, in 1941 and The greater part of the production was schedite concentrates from operations of the Nevada-Massachusetts Corand affiliated companies, which operate mills at Mill Gity Colcondenand Totilon Smaller but important producers of concentrates in 1942 werd: Nevada Schoelite, Inc., operating the Leonard mine in Mineral County; Tungsten Metals Corporation, operating the Scheelite Chief, Orable, Everitt, and Silven Bell mines in White Pine County Lincoln Mines, Inc., operating the Tem-Piute mine in Lincoln Country; Mach. L. Mining Corporation operating the M. G. L. mine in Rersbing County; and Getchell Mines, Inchesperating mines in Humboldt County :- The contentrates produced by Getchell Mines, Inc., have not/been included in the 1942 statistics because they require further milling at the Salt Lake City re-treatment plant. Of the other smaller mines producing concentrates in 1942, the largest were the Stan in Elko County, Defense Tungsten in Humboldt County, Desert Scheelite and Gunmetal in Mineral County Hand Black Mule and Tungsten

Minerals in White Pine County and the property of the property

drifts, opened several large stopes from 40 to 80 feet wide, put finger raises through from the 100-foot level to the surface, and installed a

new crushing plant.

A flotation plant was put into operation in August 1942 by Getchell Mines, Inc., and during the remainder of the year 21,675 short tons of scheelite ore averaging 0.394 percent WO<sub>3</sub> were treated, yielding 537 tons of concentrates averaging 12.69 percent WO<sub>3</sub>. treated came from the company mines in Humboldt County and from the Richmond mine, near Winnemucca, also in Humboldt County but operated by W. C. Rigg, who also has developed the Rose Creek mine in Pershing County to the productive stage. Development at the Getchell mines included 195 feet of drifts, 90 feet of crosscuts, and 97 feet of raises. Van Voorhis has described the mining and milling of tungsten ores by Getchell Mines, Inc.6

The M. G. L. mine, in Pershing County near Nixon, which has been under development for some time, made its initial output in August 1942 and during the remainder of the year produced and treated 10,233 short tons of scheelite ore, which yielded 73 tons of concentrates averaging 68 percent WO<sub>3</sub>. The mine is provided with

a modern concentrating plant.

Development was done at many other properties in Nevada in 1942, among which were the Cherry Creek and Canary Yellow in White Pine County, Star in Elko County, Silver Dyke in Mineral County, Defense Tungsten in Humboldt County, and Red Top and Red Ant in Churchill County, but lack of space precludes giving detailed information.

The tungsten deposits of the Nightingale district have been de-

scribed by Smith and Guild.7

Texas.—A small quantity of scheelite was produced by the Moore Mining Co. in 1942 near Sierra Blanca in Hudspeth County, where a small mill was erected.

The scheelite occurrences in Gillespie County have been described

recently.8

Utah.—Production of tungsten (all scheelite) in Utah was 33 short tons averaging 54 percent WO<sub>3</sub> in 1942, compared with 46 tons averaging 39 percent WO<sub>3</sub> in 1941. Shipments were 30 tons averaging 57 percent WO<sub>3</sub>, compared with 44 tons averaging 41 percent WO<sub>3</sub> Although production came from operations in Beaver, Box in 1941. Elder, Juab, and Tooele Counties, two-thirds came from the Lone Pine mine in Box Elder County. Most of the remainder came from the Star Dust mine in Tooele County and the Massae mill in Box Elder County.

In addition to the 33 short tons of high-grade ore and concentrates produced in 1942, a small tonnage of ore was mined at several properties and shipped to the re-treatment plant of Metals Reserve Co. at Salt Lake City, which was expected to begin operating in April

1943.

Washington.—Shipments of tungsten concentrates from Washington were 73 short tons averaging 35.48 percent WO<sub>3</sub> in 1942, compared with 121 tons averaging 33.91 percent in 1941. Most of the pro-

<sup>•</sup> Van Voorhis, B. W., Jr., Mining Gold, Arsenic, and Tungsten Ores at the Getchell Mine: Mining World, vol. 4, No. 12, December 1942, pp. 5-8; How Getchell Treats Tungsten, Arsenic, and Gold Ores in Its Remodeled Mill: Mining World, vol. 5, No. 3, March 1943, pp. 9-13.

† Smith, W. C., and Gulld, P. W., Tungsten Deposits of the Nightingale District, Pershing County, Nev.: Geol. Survey Bull. 936-B, 1942, pp. 39-58.

† Bureau of Economic Geology, Texas University, Scheelite in Gillespie County, Tex.: Mineral Resource Survey Circ. 55, 1942, 3 pp.

duction again came from the Germania mine near Fruitland, Stevens County, where the General Electric Co. worked over surface float and tailings to recover 19 tons of wolframite concentrates averaging 65 percent WO3 and 45 tons of wolframite jig concentrates averaging 14 percent WO<sub>3</sub>. Comparatively small quantities of wolframite concentrates were produced by James Keeth, Industrial Tungsten Corporation, Roy B. Greene, and W. H. West in Stevens County, and by the Zellweger Mining Co. in Okanogan County. W. H. West installed a jig mill at his mine in 1942, and the Zellweger Mining Co. had a small jig mill partly installed at the close of the year.

The tungsten deposits at Silver Hill, Spokane County, have been

described by Page.9

# FOREIGN TRADE 10

Domestic production of tungsten is inadequate for requirements. and the United States imports both tungsten concentrates and products, chiefly the former. Receipts of imported ore and concentrates established a new high in 1942 and amounted to 15,085,793 pounds (tungsten content), equivalent to 15,851 short tons of 60 percent WO<sub>3</sub>. Although ore and concentrates were received from 15 foreign countries in 1942, three—Bolivia (43 percent), China (30 percent), and Argentina (17 percent)—supplied 90 percent of the total.

Imports in 1942 for consumption amounted to 14,004,257 pounds (tungsten content), equivalent to 14,715 short tons of 60 percent WO<sub>3</sub>; Bolivia, China, and Argentina supplied 47, 28, and 16 percent, respectively, of the total. In addition, 6,115 pounds of tungsten in concentrates were imported from Argentina (duty free) for smelting,

refining, and export.

Tungsten ore and concentrates imported into the United States in 1942, by countries, in pounds

	General i	mports 1	Imports for co	nsumption 2
Country	Gross weight	Tungsten content	Gross weight	Tungsten content
Argentina. Australia. Belgian Congo. Bolivia. Brazil. Canada. China. Egypt French Indochina.	264, 008 13, 045, 647 85, 134 32, 417 8, 602, 346	2, 532, 468 6, 269 147, 829 6, 550, 135 44, 130 7, 272 4, 487, 399	4, 333, 411 28, 481 264, 458 13, 129, 518 85, 134 32, 417 7, 506, 059 411, 009 37, 597	2, 314, 038 15, 273 147, 829 6, 589, 045 44, 130 7, 272 3, 888, 498 218, 903 21, 418
India, British Mexico Peru Portugal Southern Rhodesia Thalland Union of South Africa	763 159, 113 433, 433 365, 637 51, 704 358, 310	518 79, 104 222, 272 186, 750 27, 963 204, 420 281, 239	763 152, 813 511, 932 456, 569 51, 704	518 76, 106 264, 586 234, 107 27, 963
Total: 1942	29, 192, 938 26, 395, 708	15, 085, 793 13, 152, 716	\$ 27, 281, 907 \$ 23, 850, 011	<sup>3</sup> 14, 004, 257 <sup>3</sup> 11, 522, 190

Comprises ore and concentrates received in the United States; part went into consumption during year, and remainder entered bonded warehouses.
 Comprises ore and concentrates withdrawn from bonded warehouses during year (irrespective of time of importation) and receipts during year for consumption.
 In addition, following quantities were imported for smelting, refining, and export—1942: 12,000 pounds containing 6,115 pounds of tungsten; 1941: 48,196 pounds containing 27,558 pounds of tungsten.

Page, L. R., Tin and Tungsten Deposits at Silver Hill, Spokane County, Wash.: Geol. Survey Bull. 931-H, 1942, pp. 177-203.
Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

The duty on tungsten ore or concentrates is 50 cents per pound on the metallic tungsten contained therein. This is equivalent to \$7.93 per short ton unit. I mention to such at layouse of specific burners of tungsten are and concentrates from the United States are insignificant and amounted to only 15,714 pounds in 4942. If on July to December 1941, exports were 2.616 pounds; exports of tungsten one and concentrates before July 1, 1941, are not separately recorded. Imports of tyngsten metal were 4,435 pounds (tyngsten content), compared with 36,793 pounds in 1941 content of ferrotungsten tyngsten carbide, tungstic acid and other compounds of tungsten for combination containing tungsten or tungsten carbide were imported in 1942.

Exports of metal, wire, shapes, and alloys other than igrotungsten were 313,223 pounds in 1942, compared with 195,762 pounds in 1941. In 1942 exports of ferrotungsten were 297,108 pounds, and from July to December 1941 they were 5,480 pounds of Exports of socium tungstate. tungstic acid; and tungstic bxide in et 1,419,189, and 11 pounds; respectively; in 1942; they were 58, 10; and none, respectively, from September dio December 1941 a Exports of ferrotung stehn before July leand of sodium tungstate at ungstice acide and tungstice exide before September 11,0194 by were not separately recorded to demodif A in 1942, three Bolivia (43 percent), China (30 percent), and Argen-

tina. (17 percent)—szzwedna normania (17 percent)

bruced 762, 200. 4. of belaurous actiques and 200. 1. at roand Consumption of tungsten ore and concentrates in the United States was about 18,300 short tons (60 percent WO, basis) in 1942, compared with 17,500 tons in 1941. Of the total consumed in 1942, about 68 percent was converted to ferrotungsten the form in which most of the tungsten is introduced into steel. However, high-purity tungsten concentrates are charged directly to the steel bath, and 17 percent of the total was so used in 1942 m. Metallic tungsten required about 10 percent of the total tungsten ore and concentrates consumed in 1942, and various tungsten chemicals absorbed the remainder (5 percent).

The chief use of tungsten, according to quantity, is in the manufacture of cutting tools, the majority of which are made of high-speed steel containing about 18 percent tungsten, 4 percent chromium, and 1 percent vanadium commonly known as "18-4-1." Smaller quantities of tungsten are used in numerous other types of high-speed steels. Molybdenum-tungsten high-speed steels (which contain 1 to 2 percent tungsten and 5 to 10 percent molybdenum) are being used successfully for many applications of tungsten high-speed steels. Other important uses of tungsten are in armor-piercing projectiles, stellite and tungsten carbide cutting tools, magnet steels, austenitic valve steels and valve seats, and erosion-resisting gun liners. Minor amounts of tungsten are used in lamp and radio-tube filaments, X-ray targets, and electrical contact points. Tungsten salts are used in the chemical, pigment, and tanning industries.

t fieldgene over eine omeentende production was the consequence of and well the consequence of the control of t And control for either the field of the control of the cont Because of restrictions on the publication of statistics by many governments, a record of recent production in many countries is not available. or and deep with the analytic and appearance of the state 
539250 - 43 -- 44

<sup>&</sup>lt;sup>11</sup> A unit, as applied to tungsten ores, is 1 percent of a top of tungsten trioxide (WO2). Thus, a short-ton unit is 20 pounds of WO3 or 15.86 pounds of tungsten (W).

World production of tungsten ores, 1937–42, by countries, in metric tons of concentrates containing 60 percent  $WO_3^{-1}$ 

[Compiled by B. B. Waldbauer]

Country 1	1937	1 <b>93</b> 8	1939	1940	1941	1942
North America:				6	32	20
Canada Mexico United States (shipments)	33 3, 175	76 2,761	118 3,889	112 4,825	99 5, 957	10 8, 46
	3, 208	2,837	4, 011	4, 943	6,088	8, 77
South America: Argentina Bolivia (exports)	866 1,802	1, 195 2, 530	1, 309 3, 33 <u>7</u>	1, 417 4, 183	1, 720 4, 353 35	2, 20 5, 60
Brazil (exports) Chile Peru	6 18 78	2 5 170	(2)	(²) 290	(2) 337	(2) 37
	2,770	3, 902	(2)	(2)	(2)	(3)
Europe: France. Great Britain: Cornwall. Italy. Norway Portugal Spain. Sweden.	148 3 3 2,069 250 127	22 258 4 19 2,810 215 180	(2) (2) (3) (3) 31 3,851 (2) 200	(2) (2) (2) (2) (2) 4, 858 299 (2)	(2) (2) (2) (2) (2) 5, 834 504 (2)	(2) (2) (2) (2) (2) (2) (2) (2)
	2,600	3, 508	(2)	(2)	(2)	(2)
Asia: Burma China (exports) Chosen India, British Indochina: Tonkin	7, 393 17, 895 2, 058 15 648	7,796 13,387 (2) 12 545	9, 025 11, 580 (²) (²) 510	(2) 3, 118 (3) (2) (3) 392	(2) (2) (2) (2) (2) (2)	(2) (2) (2) (2) (2) 3 13
Malay States: Federated Unfederated Netherlands Indies Thailand	1,077 279 (4) 221	749 333 (4) 251	246 362 2 378	108 427 (4) 400	(2) (2) (2) (2)	(2) (2) (2) (2)
	29, 586	<b>(</b> 2)	(2)	(2)	(2)	(2)
Africa: Belgian Congo Egypt Morocco, French Nigeria. Southern Rhodesia. South-West Africa Tanganyika Territory Uganda. Union of South Africa.	193 9 275 41 2 2 40	(2) 7 49 329 48 5 2 127	(2) 237 270 50 (4) 2 100	63 15 (2) 131 221 24 2 (2) 105	(2) 43 (2) 268 3 62 (2) (2) 5 112	(2) (3) (2) (2) (2) (2) (2) (3)
	562	(3)	(2)	(2)	(2)	(2)
Oceania: Australia: New South Wales Northern Territory Queensland Tasmania New Zealand	66 345 110 345 28	113 515 167 390 54	(2) 354 107 472 49	(2) 320 (3) (3) (4)	(2) (2) (3) (4) (7) 79	(3) (3) (3) (2) (4)
	894	1, 239	(2)	(2)	(2)	(3)
	39, 620	4 38,000	6 40, 000	(3)	(2)	(2)

<sup>&</sup>lt;sup>1</sup> In addition to countries listed, tungsten ore is produced in Cuba, Japan, U. S. S. R., and Western Australia, but data on production are not available.

<sup>2</sup> Data not available.

<sup>3</sup> January to June, inclusive.

<sup>4</sup> Less than 1 ton.

<sup>5</sup> January to October, inclusive.

<sup>6</sup> Estimated.

Argentina.—Argentina ranks second to Bolivia as a producer of tungsten in South America. Output comes principally from the Provinces of San Luis and Córdoba; much smaller amounts are produced in San Juan, Catamarca, Mendoza, and La Rioja. Production was 2,008 and 1,564 metric tons (66 percent WO<sub>3</sub>), respectively, in 1942 and 1941. Exports were 1,636 metric tons averaging 66 percent WO<sub>3</sub> (all to the United States) in 1942.

Australia.—The principal sources of tungsten in Australia are mines at Grassy, King Island; Storey's Creek, Tasmania; Hatch's Creek and Wauchope, Northern Territory; Banks Island, Torres

Strait; and Wolfram Camp, Queensland.

The King Island Scheelite Co. is the Commonwealth's largest pro-icer. During the year ended October 31, 1942, it milled 32,200 long tons of ore, which yielded 242 tons of concentrates; in 1941 it milled 29,250 tons of ore and re-treated 18,870 tons of tailings, which yielded 204 and 17 tons, respectively, of concentrates. The company plans to erect a new concentrating mill to treat 20,000 tons of ore monthly.

Bolivia.—Bolivia is the largest tungsten producer in South America. Most of the deposits are in the Departments of La Paz, Oruro, Potosí, and Cochabama. The principal mineral is wolframite with some scheelite. Output (as indicated by exports) was 5,606 and 4,353 metric tons (60 percent WO<sub>3</sub> basis), respectively, in 1942 and 1941.

Canada.—An intensive search for tungsten ores was under way in Canada during 1942, and as a consequence many deposits were found. The distribution of the ores has been discussed by Eardley-Wilmot.<sup>12</sup> Output of tungsten concentrates was 218 short tons (62) percent WO<sub>3</sub>) and 41 tons (51 percent WO<sub>3</sub>), respectively, in 1942 and 1941. Output was from six provinces and the Northwest Territories in 1942, but most of it was from British Columbia, Northwest Territories, and Ontario.

Nigeria.—The tungsten deposits of Nigeria have been described in considerable detail by Haag.<sup>13</sup>

Peru.—Production of tungsten in Peru is relatively small, but since 1937 it has increased progressively and amounted to 370 metric tons (60 percent WO<sub>3</sub> basis) in 1942. Exports of ores and concentrates were 337 metric tons in 1942, compared with 322 tons in 1941; figures for WO<sub>3</sub> content of the exports are not available. The principal productive mines are in the Departments of La Libertad, Ancash, Puno, and Huancavelica. There was considerable activity in developing and expanding production in 1942. The Cia. Minera Tauca, after delays caused by poor mill construction, began producing concentrates in August 1942 at Ogapita, Department of Ancash. At Pasto Bueno, Department of La Libertad, the Banco Minero del Peru installed a tungsten concentrator of 30 to 40 tons daily capacity to handle custom ores from small mines in that region. 150-ton gold-tungsten plant for treating oxidized gold ores containing tungsten was being constructed at the Tentadora mine near Lircay, Department of Huancavelica. In the Mundo Nuevo area, Department of Ancash, power plant and drilling equipment were being installed preliminary to erection of a small gravity tungsten concentrator.

<sup>&</sup>lt;sup>12</sup> Eardley-Wilmot, V. L., Tungsten—Canadian and World Situation: Canadian Min. and Met. Bull. 367, November 1942, pp. 437-454.

<sup>13</sup> Haag, H. L., Wolfram in Nigeria, with Notes on Cassiterite, Wolfram, and Columbite Zones: Min. Jour. (London), vol. 220, No. 5609, February 20, 1943, pp. 94-95; No. 5610, February 27, 1943, pp. 107-108; No. 5611, March 6, 1943, pp. 118-119; No. 5612, March 13, 1943, pp. 131-132.

# **BAUXITE AND ALUMINUM**

By John H. Weitz and M. E. Trought 1

# SUMMARY OUTLINE

	Pag	
Summary	68	5 Aluminum 6
Salient statistics	68	
Bauxite		7   Consumption 6
Production		
Consumption	69	0 Foreign trade 7
By industries	69	1 Technologic developments 7
Aluminum		1   War measures 7
Abrasive and refractory		World bauxite and aluminum industries 7
Chemical		Review by countries
Other		4
Prices		$oldsymbol{4}$
Foreign trade		

# SUMMARY

As the Nation fought through the first full year of its greatest war, aluminum became one of the most important metals in the war Without the vast tonnages of the vital white metal, produced by a rapidly expanding domestic industry, the unprecedented number of bombing and fighting planes now giving air superiority to the United Nations over large areas of the earth's surface could not have been produced. Production (521,106 short tons) and consumption (588,522 tons) of primary aluminum in 1942 advanced 69 and 94 percent over 1941. The annual rate of production at the end of 1942 had risen to 720,000 tons, and the total output in 1943 should substantially exceed 900,000 tons. Imports from Canada are expected to aggregate about 225,000 tons in 1943, making the total available supply of primary aluminum more than 1,125,000 tons. Sproduction in 1943 is estimated at an additional 293,000 tons. Secondary

Highlights of the industry in 1942 included the following: Eight Government-owned, Aluminum Company-operated reduction plants were begun or completed; the Olin Corporation became the third domestic producer of aluminum; two large Government-owned alumina plants were built, and one of them began operations in the fall; and plans were made for constructing lime-soda-sinter units at the four large Bayer-process plants. In May 1943, construction of the new lime-soda-sinter units was well under way; production had begun at the new Government-owned alumina plant at Baton Rouge, La.; and operations were scheduled to start in the Government-owned

alumina plant at Salt Lake City, Utah.

Recovery of secondary aluminum increased 86 percent in 1942. Imports and exports of crude and semicrude aluminum in 1942 increased 736 and 419 percent, respectively, compared with 1941.

 $<sup>^1</sup>$  Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce. 685

おいかいからりますのでしていている

Production (2,768,343 short tons) and consumption (2,820,525 tons) of bauxite in 1942 increased 176 and 46 percent, respectively, compared with 1941. As with aluminum production, the large output of bauxite in 1942 will be dwarfed by the 1943 production, estimated at nearly 7,000,000 short tons. Imports of bauxite, reduced by a shortage of ships and enemy submarine action, are estimated at about 1,000,000 short tons in 1943. Of the total estimated 1943 supply of nearly 8,000,000 tons, estimated requirements will take about 5,550,000 tons, and the remainder will be stocked by the Government and private industry. The allocation order, effective August 1, 1942, to conserve and direct the distribution of bauxite and alumina assures that the most essential uses are met by allocating the bulk of the high-grade bauxite to the alumina and abrasive industries.

In 1942 imports of bauxite (990,323 short tons, 76 percent of which came from Surinam) decreased 21 percent from 1941, while exports (dried equivalent) rose 35 percent. Of the domestic and foreign bauxite consumed, the alumina industry used 79 percent; chemical, 9 percent; abrasive and refractory, 11 percent; and other industries, 1 percent. Compared with 1941, the aluminum industry increased its consumption of bauxite approximately 67 percent; abrasive and refractory, 19 percent; and all other, 14 percent; whereas bauxite used in the chemical industry decreased 22 percent. Domestic ore was equivalent to 59 percent and imports to 41 percent of the total bauxite consumed. Shipments from Arkansas mines comprised 94 percent of the total domestic production, and output in Georgia, Alabama, and Virginia rose substantially above that in 1941. The average value actually received for all grades of ore shipped in 1942 dropped 9 percent from 1941.

World production of bauxite is believed to have increased 24 percent and of aluminum 35 percent in 1942. United Nations output of aluminum and bauxite in 1942 was estimated at 59 and 65 percent of the world totals and will be even larger in 1943.

Salient statistics of the bauxite and aluminum industries in the United States, 1940-42

		1940	1941	1942
Bauxite: Production (mine shipments)	short tons	401 700	1 001 477	0.500.04
Value 2	SHOPT TOHS	491, 583 \$2, 578, 968	1, 001, 475 \$5, 358, 976	2, 768, 34; \$12, 934, 02;
	short tons	705, 098	1, 250, 532	990, 32
Exports (including concentrates)2		91, 743	150, 916	291, 87
World production 3	do	5, 222, 000	7, 338, 000	9, 123, 000
Aluminum:				
Primary production	do	206, 280	309, 067	521, 106
Value		\$75, 292, 000	\$100, 395, 000	4 \$150, 768, 000
Quoted price per pound 5		18. 7	16. 5	6 15. (
Secondary production		80, 362	106, 857	198, 492
Imports		\$5, 159, 924	\$3,827,543	\$37, 123, 657
Exports		\$22, 437, 125	\$6, 872, 522	\$26, 865, 444
World production 3	short tons	916, 000	1, 216, 000	1, 644, 000

Dried bauxite equivalent.
 As shipped.
 Estimated.
 Shipments.
 New York: 99 percent plus, pure virgin ingot, according to Metal Statistics, 1942, published by American Metal Market.
 Ceiling price.

stripping jobs were in progress higher 1942 in other sections. A large new drying plant more than doubling Republic's drying capacity was constructed during 1942 at Royrotogog put into operation early in 1943; maximum production is expected by August 1943. Reynolds A new all time high was recorded in 1942 when bauxite production (think shipments converted to a dried-equivalent basis) in the United States increased 176 percent in quantity and 141 percent in value over 1941: Production rose 187 percent in Arkansas, 46 percent in Alabama 0440 percent in Georgia and 58 percent in Nirginia A small production was recorded from Mississippi and batxite was promining throughout the year. Sweet. 1401 ngnivib otasta tantini boutb Mines in Saling and Pulaski Counties, Ark produced 94 percent of the total domestic output in 1942. American Cyanamid & Chemical Colparation operated the Rauch, Heckler, and England mines in Pulaski County and the Townsend, Ozark Nov 24, Globe No. 28, Cargill, Fletcher, Quapaw, and Gates (Consolidated) mines in Saline Country Mining swass done underground aby the room-and-pillar method at the Rauch Lease, Heckler, Globe No. 28, and Gates prope erties; all other mining was open-pit. Large-scale stripping was carried on by dragline at the England, Cargill, and Fletcher properties, and mining began in September. The company's West Bauxite processing plant was idle in early 1942, but dried bauxite for the Republic Mining & Mfg. Co. during the latter part of the year. The Bierman property was developed by Consolidated Chemical Industries, Inc., and a shaft was sunk in 1942 preparatory to underground mining in 1943. Crouch Mining Co., Inc. (owned by General Abrasives Co.), mined and calcined ore from its Young mine, developed in 1941, solely for the abrasive industry. Dixie Bauxite Co. Inc.; continued operations on its Dixie No. 2 underground mine and began underground mining at its Dixie No. 3 property. The calcining mill was dismantled and sold to Bauxite Co. of Alabama in the fall of 1942, and Dixie Bauxite Cox was engaged solely in producing highgrade bauxite for the aluminim industry. Dulin Bauxite Co., Inc., produced over from its Reichardt mine throughout the year and stripped overburden from a large area. The Harley open-pit mine began operations late in May and closed temporarily during November and December 1942 and additional development was done on the Thorpe lease, which will be mined in 1942. The old Consolidated-Harris mine was reopened and some ore removed in December. A calcining kiln was installed by Dulin Bauxites Co.; Inc., during 1942 to calcine high-grade ore for the abrasive industry we Harding Prewitt Bauxite Co. began mining in December from its open-pit property in Pulaski (County for the Metals, Reserve CounThe Porocel Corporation rerected a new plant at Bergery Bulaski County, ito manufacture an gisomerization hatalyst made from downron activated bauxita impregnated with analydrous aluminum bloride for suse in the prod in the Enfants area in Barbonilozze doitaive Sentonalpid/homenturb TO Republic Mining all Migo Correspection year Aluminum Con of America) the principal domestic producer rextended its previous open-pit mining operations; open-pit mining was done in secs. 10, 14, 15, 116,127, (T) 2.S., R. 14 (W.) Saline County, and major overburden Chemical Corporation mereased production at its Thig Pen mine and operated an oil-fired drying kiln nearby, and Benjamin Easterlin shipped a small quantity of ore before abandoning his mine late in Republic Mining & Mfg. Co. opened a drying plant in Ployd

stripping jobs were in progress during 1942 in other sections. new drying plant more than doubling Republic's drying capacity was constructed during 1942 at Bauxite and put into operation early in 1943; maximum production is expected by August 1943. Mining Corporation operated its Covington and Hurricane underground mines near Brooks, Saline County, in 1942, after sinking shafts through difficult ground in early fall, and during the latter half of 1942 conducted extensive stripping operations at the Sherrill property in Pulaski County. Sweet Home Bauxite Co. began operations at its open-pit Sweet Home mine in Pulaski County in May and continued mining throughout the year. Sweet Home Mining Co. stripped its Hurricane Creek property in Saline County and began mining early Victory Bauxite Co. opened its Weiss open-pit mine in Pulaski County in November and continued mining until April 1943; the company will open a new property in 1943 in Saline County. New Arkansas producers in 1943 will include the Bauxite Drilling & Testing Co., S. E. Evans Construction Co., and a new company to operate the Maner Graham and Billy Bridewell properties.

Bauxite shipped from mines in the United States, 1938-42, by States

			Short tons	an ing palawa. Bandangan meru		
State and year				To	tal	Value, f. o. b.
	Crude	Dried	Calcined	As shipped	Dried- bauxite equivalent	mine, as shipped
Alabama and Georgia:				•		
1938	6, 196	1 14, 047		20, 243	19, 323	\$132,883
1939	3,054	12,676		15, 730	15, 251	91, 28
1940	2 2, 646	10, 463		2 13, 109	3 12, 747	2 77, 57
1941	2 74, 069	25, 851		3 99, 920	3 89, 830	<sup>2</sup> 406, 13
1942	s 112, 397	60, 751		<sup>3</sup> 173, 148	3 155, 922	<sup>3</sup> 904, 61
Arkansas:	00 540	010 000	1.00.00=	900 454	000 000	1 000 00
1938 1939	- 80, 749	218, 338	1 29, 387	328, 474	328, 903	1, 679, 66
1010	111, 121	252, 398	4 41, 088	404, 607	405, 093	2,074,95
1940	128,712	292, 435	4 52, 930	474, 077	478, 836	2, 501, 39
1942	247,898	596, 708	4 66, 564	911, 170	911, 645	4, 952, 83
Total United States:	1, 367, 237	1, 318, 622	4 81, 456	2, 767, 315	2, 612, 421	12, 029, 40
1938	86, 945	1 232, 385	1 29, 387	348, 717	348, 226	1,812,54
1939		265, 074	4 41, 088	420, 337	420, 344	2, 166, 23
1940	131, 358	302, 898	4 52, 930	487, 186	491, 583	2, 578, 96
1941	321, 967	622, 559	4 66, 564	1,011,090	1,001,475	5, 358, 97
1942	1, 479, 634	1, 379, 373	4 81, 456	2, 940, 463	2, 768, 343	12, 934, 02

<sup>&</sup>lt;sup>1</sup> Includes small quantity of activated.

The production of bauxite in Alabama increased during 1942, but the percentage increase recorded was lower than in any other State. Bauxite Co. of Alabama, Barbour Bauxite Co., Republic Mining & Mfg. Co., Floridin Co., and D. M. Wilson Bauxite Co. were active in the Eufaula area in Barbour and Henry Counties. New driers were built in early 1943 by Bauxite Co. of Alabama and Barbour Bauxite Co. to dry ore for the chemical industry. J. C. Hebble ceased mining near Asheville, St. Clair County.

At Andersonville, Sumter County, Ga., American Cyanamid & Chemical Corporation increased production at its Thig Pen mine and operated an oil-fired drying kiln nearby, and Benjamin Easterlin shipped a small quantity of ore before abandoning his mine late in 1942. Republic Mining & Mfg. Co. opened a drying plant in Floyd

<sup>Includes Virginia.
Includes Mississippi and Virginia.
Includes sintered.</sup> 

County and produced a small amount of ore from its Booger Hollow mine. H. G. Bradhaw and General Ore Co. also produced small quantities of ore from the Hermitage area in Floyd County. Bethlehem Co. mined for a short time at its Irwinton and Toomsboro mines and is planning to construct a small drier in Wilkinson County.

Republic Mining & Mfg. Co. continued to mine near Spottswood, Augusta County, Va., operating the Allen, Harris, and Lightner properties. J. W. Adams mined a small tonnage of ore from the

Flora mine in Kemper County, Miss., in the fall of 1942.

A canvass of producers, conducted by the Bureau of Mines in November 1942, indicated that 1943 bauxite production will approach 7,000,000 short tons. It is estimated that known domestic reserves of what are at present considered commercial grades of bauxite will not last more than 3 years at the expected 1943 depletion rate. In realization of the precarious condition of bauxite reserves, the Bureau of Mines and the Federal Geological Survey in the fall of 1941 initiated an extensive drilling and exploration program in all States where

bauxite deposits were known or thought to occur.

Stratigraphic studies in the Coastal Plain had shown that all known bauxite deposits in the province were associated with the Midway-Wilcox contact, and reconnaissance work was done along this horizon from Georgia to Texas by the Geological Survey in an effort to locate new areas in which bauxite deposits might be expected. Some areas that warranted further exploration were found, but the greatest value of the preliminary work was to eliminate large areas from further consideration. The largest Geological Survey party worked in Arkansas in cooperation with the Bureau of Mines drilling project and collected and assembled geologic information, made aerial and subsurface maps of selected districts, made drilling recommendations, and furnished other geological advice. In the eastern Gulf Coastal Plain drilling recommendations were made for three areas in Mississippi, two in Alabama, and two in Georgia. All the known deposits in the Appalachian Valley were examined and drilling recommendations were made for two districts in northwestern Georgia, two in northeastern Alabama, and one in Tennessee. Cooperation was also extended by the Survey in locating and logging drill holes and in furnishing information for the war minerals reports on bauxite prepared by the Bureau of Mines.

In Arkansas the Bureau of Mines covered 1,400 square miles in Pulaski and Saline Counties by geophysical surveys in 1942 and drilled 573 holes, with an average discovery of more than 10,000 long tons of bauxite per hole. The total footage drilled was 134,900, and 208 or 36 percent of the holes were in bauxite. Eight deposits were delimited by drilling and an estimated 3,650,000 long tons of marketable ore indicated. Reduced to a mined and dried basis, the total commercial ore discovered was approximately 1,912,500 long tons or 2,142,000

short tons.

At Eufaula, Ala., and Andersonville, Ga., Bureau drilling has disclosed considerable tonnages of marketable bauxite, and further exploration is being actively carried on in these areas. Initial prospecting disclosed 929,000 long tons of marketable ore, which on a mined and dried basis is approximately 670,000 long tons or 750,000 short tons. Drilling at Rock Run, Ala., and Chattanooga, Tenn., during 1942 gave disappointing results, disclosing only very small tonnages of marketable ore.

w.Stocks of bauxite on hand at mines and processing plants on December 31, 1942, totaled 294,337 short-tons (dried bauxite) equivalent) compared with 174,023 non-December 31, 1944. Stocks at the sumers' plants increased from 593,849 tons at the beginning of the year to 959,082 at the endy Metals Reserve; Company stock piles dons tained 479,207 tons at the end of 1942. O glM & gmmM sidning Metals but and but gmt area of vituo as a pure

Adams mined a small tonnage of ore from DIO off County, Miss, in the fall of 1942 aniM to use the But ummed states (defrestic) percenting whom to 1942, indicated thousand who who wisite oreside alson tadt betamute റെ**ട്ട് 50 <del>ിംഗി</del>** t present considered commercial grades a ore the pected 1943 depletion rate. al predictors doudition of bankite reserves, the Bu ines and the Federal Geological Survey in the fall of 1941 initia W 3000 Rt Harm its deposits were known or thought to occur Stratigraphic studies in the Coastal Plain had shown that []3 xite deposits in the province were edf dtigo beteinoese way-Wicox contact, and reconnaissance work prizon from Georgia to Texas by the Geological Survey in an new areas in which bauxite deposits thight beorgos ed. areas that warrented further exploration were found, ball of the preliminary work was to climinate large The threest Geological Survey consideration. as in cooperation with the Bureau of Min 884 12 assenab ed population unit formation, and brin selected districts, made drilling red naps o dπο 600 ± α Ι (loasta) ude for three a All the km To Exports moof) (1910) ten 1915 on (1920) ontaines wit 1930 beau 1936) w

also extendesion such a few parting of the manus of the mainter of address and in furnishing information for the war numerals reports on bauxite prepared by the Bureau of Min**repression** 

Actual domestic consumption of bauxite (as determined by special monthly consumer surveys conducted by the Bureau of Mines for Federal war, agencies) totaled 2,820,525 short tons (dried bauxite equivalent) in 1942 and compared with a consumption of 1,928,052 tons in 1941. The 1941 figure includes exports to Canada, as virtually all bauxite shipped there during that year was destined to American-owned abrasive plants for the manufacture of crude abrasives returned to the United States for final manufacture and consumption. The 1942 figure includes bauxite shipped to abrasive plants in Canada but does not include approximately 100,000 tons of dried ore shipped to the Canadian aluminum industry. Consumption of the 2,820,525 tons was as follows: Alumina industry, 2,229,157 tons; chemical, 256,479; abrasive (including refractories), 302,557; and cement, oil refining, steel, and ferro-alloy industries, 32,332 tons. Consumption

during 1942 gave disappointing results, disclosing only very small tournages of marketable orc.

60) 60)

TO THE CANAL CONTRACTOR AND ASSESSMENT OF THE PARTY OF TH

of bauxite "as shipped" totaled 2,742,573 tons and consisted of 430,486 tons of crude bauxite, 2,124,450 tons of dried, 180,337 tons of calcined and sintered, and 7,300 tons of activated ore. Of the bauxite consumed (dried equivalent basis), 41 percent was foreign and 59 percent domestic ore. The alumina industry used 94 percent and the chemical industry 4 percent of the foreign ore About 2 percent of the foreign ore was employed in abrasives, eements, and other uses.

Apparent domestic consumption, shown in the table below is presented from two different points of view; and apparent consumption within the United States does not correspond with the data above, inasmuch as the calculations are based upon "shipments" to domestic plants and do not consider fluctuations in consumers stocks.

Shipments, imports, exports, and apparent consumption of bauxite in the United States, 1938-42, in short tons

		[Dr	lea-bauxite e	dmaster.	ष: 🚉	75 TE SE	138.6	\$., to
	Domestic shipments from miner and processing plants to industry				803	14 E E	Apparent	Apparent consumption, in-
Year	Arkansas	Alabama and Georgia <sup>2</sup>	Total	Impor	ts: 25	Exports Follow	tion within United States	cluding shipments to Canada for process- ing 1
1938	308, 088 375, 925 490, 107 960, 741 2, 588, 637	19, 323 15, 331 2 12, 995 2 89, 389 2 153, 663	327, 411 391, 256 503, 102 1, 050, 130 2, 742, 300	510, 3 582, 6 705, 0 1, 250, 5 990, 3	98 98	101, 182 96, 925 134, 462 244, 934 329, 477	736, 605 876, 932 1, 073, 738 2, 065, 728 3, 403, 146	819, 800 971, 000 1, 200, 600 3 1, 928, 052 3 2, 830, 525

<sup>1</sup> Includes exports to Canada, inasmuch as virtually all of this bauxite is shipped to American-owned plants in Canada for manufacture into crude abrasives ceimported into the United States for final manufacture and consumption.

2 Includes Virginia in 1940 and 1941 and Virginia and Mississippi in 1942.

3 Actual consumption.

#### BY INDUSTRIES

2822

The following table shows only shipments of domestic bauxite to

consuming industries and excludes foreign ore.

Aluminum.—Actual consumption of bauxite by the aluminum industry increased approximately 67 percent over that in 1941 and comprised 79 percent of all the domestic and foreign ore used. industry employed dried and undried ore from Alabama, Arkansas, Surinam, British Guiana, and Brazil. Estimated bauxite consumption in 1943 is expected to be about 118 percent above that in 1942.

Abrasive and refractory.—Manufacturers of crude aluminous abrasive pigs in Canada and the United States received approximately 19 percent more domestic bauxite in 1942 than in 1941, being consigned 6 percent of all the domestic ore shipped to industry. Except for a small quantity from British Guiana, all of the calcined and sintered ore employed came from Arkansas. The industry's 1943 ore requirements are expected to exceed those of 1942 by about 33 percent. The use of bauxite in refractories is combined with abrasives. In 1942 the consumption of special aluminous refractory products increased substantially over 1941 in the steel, glass, ship, and other industries.

# Bauxite shipped from mines and processing plants in the United States, 1938-42, by consuming industries, in short tons

	19	38	19	1939		940	19	1941		142
Industry	As shipped 1	Dried- bauxite equivalent	As shipped 1	Dried- bauxite equivalent	As shipped 1	Dried- bauxite equivalent	As shipped 1	Dried- bauxite equivalent	As shipped 1	Dried- bauxite equivalent
Aluminum <sup>2</sup>	161, 513 71, 613 54, 879 11, 572	161, 513 70, 952 83, 568 11, 378	180, 329 91, 217 61, 987 15, 947	180, 329 89, 080 92, 205 29, 642	240, 947 92, 735 90, 522 14, 254	239, 897 90, 645 144, 276 28, 284	618, 763 161, 037 148, 562 51, 370	597, 607 158, 294 237, 980 56, 249	3 2, 445, 365 183, 804 170, 060 47, 366	3 2, 266, 839 174, 826 251, 497 49, 138
Total quantity Total value	299, 577 \$1, 823, 307	327, 411	349, 480 \$2, 448, 038	391, 256	438, 458 \$3, 075, 317	503, 102	979, 732 \$6, 155, 714	1, 050, 130	2, 846, 595 \$13, 672, 727	2,742,300

<sup>&</sup>lt;sup>1</sup> Includes crude, dried, calcined, and activated, 1938–42; and sintered, 1939–42.

§ Includes some ore shipped to the abrasive and chemical industries.

§ Includes 672,000 tons (584,640 dried equivalent) shipped to Metals Reserve Co. stock piles.

§ Small quantity of bauxite shipped to makers of refractories probably included under "Abrasive."

Chemical.—The chemical industry consumed 22 percent less bauxite in 1942 than in 1941 and used 9 percent of all the domestic and foreign ore consumed. Shipments of domestic bauxite from mines and processing plants to the chemical industry increased 10 percent. Consumption by the industry in 1942 totaled 256,479 short tons of bauxite, but this includes ore used to make some aluminum chemicals other than those shown in the following table and does not include a large portion of the bauxite used in the manufacture of the alumina shown in the table. Ore used to make the aluminum salts and alumina shown in the table totaled approximately 306,880 tons. In addition to bauxite, producers of aluminum salts reported consuming 8,364 tons of alumina (calcined equivalent), 6,031 tons of primary and secondary aluminum, 19,637 tons of clay, and a relatively small quantity of beryl and chromite residue. Manufacturers estimated that their 1943 bauxite consumption will be 13 percent less than in 1942 (exclusive of a large part of the bauxite consumed in making alumina for the chemical and other industries).

Production and shipments of aluminum salts decreased 4 and 3 percent in 1942. Production of alumina increased 9 percent, but shipments decreased 7 percent. Of this alumina, only 14 percent was consumed by the producers of aluminum salts; the remainder was used in the manufacture of abrasives, refractories, petroleum products, spark plugs, glass, rubber, paints, and various other commodities.

Aluminum salts and alumina produced and shipped in the United States, 1941-42

			1941			1	1942	
	Produc- tion		Shipme	nts	Produc- tion		Shipme	nts
	Short tons	Ship-, pers	Short tons	Vålue	Short	Ship- pers	Short tons	Value
Aluminum salts: Alum: Ammonia. Potash	8, 235 4, 008 4, 250 } 16, 583 *513, 815 11, 670 *35, 401 }32, 078	39	8, 268 4, 441 4, 399 16, 180 3 515, 722 11, 768 3 34, 632 3 30, 974	\$511, 414 297, 595 184, 659 2, 545, 373 310, 569, 528 188, 980 21, 106, 024 1, 979, 102	7, 698 1 4, 154 3, 839 16, 717 504, 951 12, 940 22, 210 28, 404	7 5 6 3 6 21 9 9 9 2	7, 265 2 3, 781 3, 815 }16, 578 506, 870 12, 925 23, 331 29, 993	\$497, 830 283, 882 176, 302 2, 714, 682 11, 174, 785 204, 872 833, 378 1, 850, 200
Sodium aluminate  Total aluminum salts. Alumina 4	626, 040 53, 710	10	626, 384 56, 093	17, 382, 675 5, 602, 762	600, 913 58, 297	14	604, 558 52, 413	17, 735, 931 5, 510, 343

<sup>&</sup>lt;sup>1</sup> Includes 73 tons made from iron-free aluminum sulfate.

<sup>2</sup> Includes 71 tons made from iron-free aluminum sulfate.

<sup>4</sup> Excludes alumina produced for use in making aluminum; includes activated, calcined, crude, light and heavy hydrate, converted to a calcined-alumina equivalent. Figures not comparable with those before 1939.

by 90 percent.

Aluminum, salls shipped in imported into, and exported from the United States, bauxite in 1942 than in 1941 at 18891 9 percent of all the domestic and foreign ore consumed. I Shipments of domestic banxite from strong sing plants to the chemical industry increased mines and Jonsumption by through ustransmath the modeled 256,479 the free free includes ore used to make some 1() percent munimula radio sheathuddinos aluminun chemicale other than these shown in the following table moder a bronge postery of onthe bassite unode in the manu-Shorte Ook alter facture of the alumina shown in the table. Ore used to make the and a relatively small quantity of beryl and chromice residue. Manu-facturers estimated that their 1943 bauxile consumption will be of Karly in 1943 the Torrance Aluminum Products Co. began pro-daring somium aluminate at a plant in Torrance, Calif. The alu-inhous raw material being used is fine aliminum diossoftom West obset reduction plants: In late 1942 and early 1943 the General Chemical Co. was running from Bauxie to Clay as an aluminous raw material at all of its aluminum chemicals plants, a change of major importance as the company has been a large consumer of bauxie in past years. No central calcining plant is being built at Owensylle! Mo., which will calcine Missouri diaspore and ship the product to all General Chemical Co. widely scattered aluminum-salts plants.

Other: The use of thermally activated bauxite as an adsorbent and catalyst in the petroleum industry maintained about the same rate as in 1941 but is expected to expand substantially in 1943, as production of high-octane aviation gasoline and synthetic rubber increase. bauxite was used in fluxing ferro alloys and in high-early-strength aluminous cement. Consumption in the cement, steel and ferro-alloy, and oil-refining industries rose 14 percent above the quantity used in 1941, and it is estimated that 1943 bauxite needs will exceed 1942 use

In 1942 the average selling price, f. o. b. mines and processing plants, was \$3.84 a short ton for crude (undried) bauxite, \$4.51 for crushed dried bauxite. \$11.97 for calcined bauxite, and \$46.68 for activated bauxite. Values per long ton were as follows: \$4.30 for crude, \$5.05 for dried, \$13.41 for calcined, and \$52.28 for activated bauxite. The average value for all grades of domestic ores as shipped was \$4.80 a short ton (\$5.30 in 1941) or \$5.38 a long ton (\$5.94 in 1941). Nominal market quotations on domestic, chemical, crushed and dried bauxite rose from \$7 to \$8.50 a long ton in 1941 to \$7.50 to \$8.50 in 1942. The Metals Reserve Co. began purchasing ore in May 1942, for stock piling and for consumption in the new Hurricane Creek (Ark.) and Baton Rouge (La.) alumina plants. The price schedule, set up by the Metals Reserve Co. for purchasing bauxite, provides a base price of \$4 a long ton for ore containing 50 percent alumina and 13 percent silica, and a system of penalties and bonuses.

Alumbum selts:

ř.

was produced at Massena, adagt najagovat at Mead, Wash.; 18 percent at Troutdale, (reg., 15 percent at Jones Mills, Ark.; and 11 ab Imports of bauxite in 1942 dropped 21 percent from the peak year of 1941, whereas exports (dried equivalent) increased 35 percent 1960 the 1942 imports, 748,642 short tons came from Surinam, 238,426 from British Guiana, 3,252 from Brazil, and 3 from Canada, Byroustoms districts, importations were as follows: 892,291 tons to Mobile 69427 to New Orleans, 19,451 to Philadelphia, 9,149 to Massachusetts, 13 to Wermont, and 2-to New York, 000 of the 1942 exports 1251,509 short tons were classified as bauxite and other aluminum ores, and 40,362 tons as alumina and other bauxite concentrates More than 99 percent of the exports went to Canada; only small quantities were shipped to Argentina, United Kingdom, Iran, Orinidad and Tobago, Aust tralia, UM exico u Curação u Venezuela, Cuba, teande obea Dominican and the second Covernment expansion, about 360,000 vailduqua February 20, 1942, a contract was made between Defense Plant Cormultim Burrite imported into and experted from the United States; 1938-420 il 8 104 undertook to construct a 500,000 ton alumina plant at Baton Ja be d'Imports de cont la Exports (including | Ood ent Imports to con | Exports (including | Ood ent Imports to con | Exports (including | Ood ent Imports to con | Dauxite | Concention | 1 | Ood ent | Imports to con | Content | Ood ent 1542, and receilly, Year <u>एउडए क्लेड</u> old ni oshorto value oshortons short your yalue a Walue along algar ubber 14186 "Mainthing as follows: 1938, 72 short tons valued by \$5,464, 1939, 1 ton, \$432, 1940, 12 tons, \$1,743; 1941, 67 tons, \$5,544; 1942; 24316 tons, \$1,571,397; in single lie and single complete, and all plants in \$1,571,397; in single lie and single complete. Of a total of 36 pollines in the gradequetased are nartly constructed. by the Detense Plant Gorpannulla operated by the Aluminani Co. all but 14 were completed as of May 20, 1943. Two to four com Primary.—The production of 521,106 short tons of primary aluminum in 1942—69 percent more than the 309,067 tons produced in 1941—represented another all-time record for the aluminum industry. It was considerably more than the entire world production in 1937 but represented only about 50 percent of the ultimate annual production goal. The annual rate at the end of 1942 had risen to 720,000 tons, and the expected rate on December 31, 1943, (including all plants now operating under construction, or approved), is estimated at approximately 1,147,000 tons. Actual domestic output in 1943 should total substantially more than 900,000 tons or more than the world production in 1940. The five aluminum-reduction plants of the Aluminum Co. or approved the larger part of the Aluminum Co. or of the first produced of primary aluminum when it began operations at its plant in Taccama, Wash, in 1942. Of the Aluminum Co. output from its privately owned plants, 39 percent at Massena, N. Y. 13 percent at Badin, N. C. and 5 percent at Niagara Falls, N. Y. Of the output at Aluminum Co.-operated Detense Plant Corporation plants 31 percent at Aluminum Co.-operated Detense Plant Corporation plants 31 percent at Aluminum Co.-operated Detense Plant Corporation plants 31 percent at Aluminum Co.-operated Detense Plant Corporation plants 31 percent pleted potlines in the new promoved the during the latter part of

was produced at Massena, N. Y.; 25 percent at Mead, Wash.; 18 percent at Troutdale, Oreg.; 15 percent at Jones Mills, Ark.; and 11 percent at Los Angeles, Calif. The Listerhill (Ala.) plant of Reynolds Metals Co. supplied 55 percent of Reynolds' production, and the Longview (Wash.) plant the remaining 45 percent. The value of the aluminum shipped in 1942 averaged 14.62 cents a pound compared

with 16.24 cents in 1941.

The second Government expansion program (of February 26, 1942) providing for an additional 320,000 tons of metal has not been increased since that date, although capacity estimates have been changed on the basis of performance so that the original privately owned capacity and the early expansion financed by private and Reconstruction Finance Corporation capital now totals about 474,000 tons; the first Government expansion, about 338,000 tons; and the second Government expansion, about 360,000 tons. On February 20, 1942, a contract was made between Defense Plant Corporation and the Aluminum Co. of America whereby the Aluminum Co. undertook to construct a 500,000-ton alumina plant at Baton Rouge, La., in addition to the 500,000-ton plant already approved at Hurricane Creek (Bauxite), Ark. A 150,000-ton addition to the Hurricane Creek plant was begun in February 1942; and recently, owing to the unexpectedly high production of metal per potline in the newer reduction plants, another expansion of 127,500 tons was announced for Hurricane Creek. The Kalunite, Inc., alumina plant at Salt Lake City, Utah, originally scheduled for 10,000 tons annual capacity, was expanded twice to 30,000 and finally to 36,000 tons.

All but one reduction plant in the first expansion program are essentially complete, and all plants in the second expansion program are partly constructed. Of a total of 36 potlines in the group owned by the Defense Plant Corporation and operated by the Aluminum Co. all but 14 were completed as of May 20, 1943. Two to four completed potlines in the new plants were idle during the latter part of 1942 and the early part of 1943 due to an acute alumina shortage. For this reason the alumina plants are being pushed toward completion

under AA-1 priorities as rapidly as possible.

Bauxite importation problems became acute in the summer of 1942 owing to a shortage of cargo space and to an intensive submarine campaign in Caribbean waters. This situation caused a sharp drop in imports of high-grade South American ore, and more domestic ore of a considerably lower grade had to be used to keep the alumina plants going. Realizing this fact, and with shipping prospects growing steadily worse, the War Production Board, on advice from the National Research Council, approved lime-soda-sinter units at each of the four Aluminum Co.-operated alumina plants. Owing to delays, construction was not begun on these units until January and February 1943, but they are now proceeding under AA-1 priorities and will be in partial operation by September 1943.

In addition to the expansion of reduction and alumina plants there was a large increase, part in Government-owned and part in privately owned fabricating plants, of strong alloy-sheet capacity as well as forging, extrusion, rod and bar, and casting capacity. During early 1943 bottlenecks in the fabricating program in extrusions and rod and bar facilities constituted one of the main limiting factors in the ex-

大学の一本世代を考えるようにある大

Projected annual alumina- and aluminum-producing capacity of the United States in 1944, in thousands of short tons

	Alumina	capacity	Aluminum capacity		
Operating company and plant location	Company- owned	Government- owned	Company- owned	Government- owned	
Aluminum Co. of America: East St. Louis, Ill	1 328				
Hurricane Creek (Bauxite), Ark		2 3 778			
Alcoa, Tenn Massena, N. Y Niagara Falls, N. Y			180 77 20	2 54	
Vancouver, Wash			56 91		
Los Angeles, Calif Jones Mills, Ark				9 776	
Mead (near Spokane), Wash				2 3 108	
Modesto, Calif				<sup>8</sup> 54 <sup>8</sup> 54	
Listerhill, Ala Longview, Wash Kalunite, Inc.: Salt Lake City, Utah			<sup>2</sup> .50 30		
Olin Corporation, Tacoma, Wash		3 3 3 9		² 20	
Total capacity	1, 078	1, 314	504	668	

<sup>&</sup>lt;sup>1</sup> Includes only capacity for aluminum industry.
<sup>2</sup> First expansion program.

pansion of aircraft production. This situation will be largely alle-

viated during the summer of 1943.

In 1942 the Aluminum Co. of America virtually completed its \$250,000,000 privately financed expansion of alumina, aluminumreduction, and fabricating capacity. In addition to company-owned expansion, the Aluminum Co. is building many plants for the Defense Plant Corporation which it will operate for the Government, among which are the following: Alumina plants at Baton Rouge, La. (500,000ton annual capacity) and Hurricane Creek, Ark. (777,500 tons) aluminum-reduction plants at Massena, N. Y. (54,000 tons), Troutdale, Oreg. (72,000 tons), Los Angeles, Calif. (90,000 tons), Jones Mills, Ark. (72,000 tons), Mead (Spokane), Wash. (108,000 tons), Maspeth, L. I., N. Y. (144,000 tons), Burlington, N. J. (54,000 tons), and Modesto, Calif. (54,000 tons); sheet rolling mills at Spokane, Wash. (144,000 tons), and Chicago, Ill. (144,000 tons); extrusion and tubing plants at Cressona, Pa. (30,000 tons), and Phoenix, Ariz. (33,000 tons); forging plants at Cannonsburg, Pa. (38,700 tons), Newcastle, Pa. (10,600 tons), Vernon, Calif. (19,500 tons), and Monroe, Mich. (672,000 cylinder heads annually); plants for producing cast cylinder heads for air-cooled engines at Kansas City, Mo. (1,200,000 heads), and St. Paul, Minn. (600,000 heads); and a synthetic cryolite plant at Hurricane Creek, Ark. (9,000 tons).

After the refusal of the War Labor Board to allow a general wage increase in the plants of Aluminum Co. of America in the fall of 1942, the Aluminum Workers of America and the Aluminum Co. negotiated a wage adjustment applying to the plants at New Kensington, Detroit, Bridgeport, and Edgewater, which was subsequently allowed by the Board. During early December three wildcat strikes within a week interrupted production at the Detroit plant of Bohn Aluminum &

<sup>3</sup> Second expansion program.

Brass Co. As the result of a week-long strike of the Mine, Mill, and Smelter Workers, Die Casting Division, Congress of Industrial Organizations, in die-casting plants of the Aluminum Co., the War Labor Board withheld the union's security clause for 60 days as a disciplinary measure. In January 1943 an unauthorized strike against rotating shifts took place in the New Kensington plant. downs and other labor difficulties that greatly curtailed production at the Cleveland plant of the Aluminum Co. were investigated in early February by a representative of the United States Army plantprotection service. The trouble continued, however, and developed into a walk-out, ending on February 26, 1943, after the War Labor Board ordered the discharge of 44 of the striking employees. Workers of the Republic Mining & Mfg. Co., the bauxite-mining subsidiary of Aluminum Co. of America, received a wage increase of 5 cents an hour retroactive to September 20, 1942, upon authorization by the War Labor Board in March. On April 21, 1943, a strike was called by local leaders of the Aluminum Workers of America at the Edge water (N. J.) plant of the Aluminum Co. because of grievances arising from lay-offs. The strike was not sanctioned by the international president of the union.

After dismissal of the monopoly charges brought by the Government against the Aluminum Co. of America, the Department of Justice filed an appeal to the United States Supreme Court which was allowed in September 1942 and docketed for October 20. On November 23, the Clerk of the Supreme Court sent a letter to counsel for both sides stating that four justices had disqualified themselves from acting on the controversy and therefore the required quorum of six justices was not available. The Aluminum Co. immediately moved to dismiss the appeal. The Department of Justice asked the Court to deny the motion for dismissal, stating that "there is a possibility that, if the case is retained, legislation will be enacted empowering the Court to hear the appeal through those members of the Court qualified to

participate.'

On December 10, 1942, the New York State Court of Appeals upheld the Niagara Falls Power Co. and the Aluminum Co. of America against the State Waterpower and Control Commission in two decisions maintaining the status quo in regard to waterpower of the

Niagara River.

During 1942 the Reynolds Metals Co., Federal Reserve Bank Building, Richmond, Va., completed an addition to its aluminum-reduction plant at Listerhill, Ala., bringing the annual capacity to 50,000 short tons, and this together with the 30,000-ton plant at Longview, Wash., brings the company total annual capacity to 80,000 tons. The year 1942 saw the completion of a sheet-rolling mill and rod mill at Listerhill, Ala., operated under the name of the Reynolds Alloys Co., and an extrusion plant at Louisville, Ky. At the instance of the Government, the sheet and rod facilities in Alabama are being increased in capacity by 12,000 tons, and negotiations have recently been concluded with the Defense Plant Corporation to further increase the company extrusion capacity.

The Olin Corporation (Western Cartridge Co.), East Alton, Ill., completed construction of its 20,000-ton aluminum-reduction plant

The Company of the last of the company of the compa

ている かんこうじょ あいかい かいかい かんしゅう

at Tacoma, Wash., during 1942 and began producing aluminum in September. Its subsidiary, Kalunite, Inc., constructed a 36,000-ton alumina plant at Salt Lake City, Utah, which will use alunite from Marysvale, Utah, as a raw material. The plant is expected to start operations before June 1, 1943. Both the alumina and aluminum plants were built with Defense Plant Corporation funds and are Government-owned.

Other companies that were enlarged or built new facilities in connection with the aluminum expansion program (chiefly with Defense Plant Corporation funds) were: Pennsylvania Salt Mfg. Co.—a 10,000-ton (annual) synthetic cryolite plant at Cornwells Heights, Pa.; Extruded Metals Defense Corporation—a 9,000-ton tubing and extrusion plant at Grand Rapids, Mich.; Bohn Aluminum & Brass Corporation—a 17,000-ton expansion to extrusion plant at Los Angeles, Calif.; Revere Copper & Brass Co.—extrusion plant at Baltimore, Md., and a 3,900-ton forging plant at Rome, N. Y.; Chevrolet Motor Division—a 59,040-ton forging plant at Saginaw, Mich., and a forged-cylinder-head plant at Anderson, Ind., with a capacity of 600,000 heads a year; Aluminum Forgings Co.—a 7,500-ton forging plant at Erie, Pa.; Chrysler Corporation—a 1,650-ton-forging plant at Detroit, Mich.; Tube Turns, Inc.—a forged-cylinder-head plant with a 600,000-head annual capacity; Buick Motor Co., Flint, Mich., Wright Aeronautical Corporation, Lockland, Ohio, M. L. Oberdorfer Brass Co., Syracuse, N. Y., Servel, Inc., Evansville, Ind., Ford Motor Co., Detroit and Dearborn, Mich., National Bronze & Aluminum Foundry Co., Cleveland, Ohio, Dodge Motor Co., Chicago, Ill., Caterpillar Tractor Co., Peoria, Ill., and Nash-Kelvinator Corporation, Kenosha, Wis.—cast-cylinder-head foundries; and Great Lakes Carbon Corporation—a 90,000-ton calcined-petroleum-coke

Secondary.—Recovery of secondary aluminum in 1942 totaled 198,492 short tons compared with 106,857 tons in 1941 and 80,362 tons in 1940. The 198,492 tons recovered from secondary sources included 14,104 tons of pure metal (98.5+ percent), 180,979 tons of aluminum alloys, 1,268 tons of aluminum in brass and bronze, 473 tons in zinc base alloys, and 1,668 tons of aluminum in chemical products (1,648 in aluminum chloride and 20 in sodium aluminate). Production in the form of secondary aluminum ingot totaled 144,694 tons (83,933 in 1941). The secondary aluminum recovered in 1942 required the consumption of 217,611 tons of aluminum scrap, 43,248 tons or 20 percent of which was old scrap (45,329 tons or 36 percent in 1941), and 174,363 tons or 80 percent new scrap (81,118, or 64 percent in 1941). Remelters, smelters, and refineries used 73 percent of this scrap; aluminum rolling mills, 26 percent; and foundries and other manufacturers, 1 percent. Additional information on secondary aluminum is given in the chapter on Secondary Metals—Nonferrous.

#### CONSUMPTION

Apparent domestic consumption of primary aluminum in 1942 increased 94 percent over 1941. Consumption of secondary aluminum increased at approximately the same rate.

Production, imports, exports, and apparent consumption of primary aluminum and production of secondary aluminum in the United States, 1938–42

		Prin	nary alumini	ım		Secondary aluminum		
Year Production		luction	Imports	Exports	Apparent consump-	Short tons	Value 2	
Short tons Valu	Value	(short tons)	(short tons)	tion 1 (short tons)		y alue -		
1938 1939 1940	143, 441 163, 545 206, 280	\$56, 659, 000 64, 600, 000 75, 292, 000	8 8, 870 9, 290 17, 435	6, 309 36, 632 26, 886	89, 523 167, 646 227, 017	38, 800 53, 947 80, 362	\$15, 326, 000 21, 309, 065 29, 332, 130	
1941 1942	309, 067 521, 106	100, 395, 000 4 150, 768, 000	13, 358 111, 650	7, <b>4</b> 05 38, 732	302, 788 588, 522	106, 857 198, 492	34, 707, 153 58, 039, 061	

Data not available on fluctuations in consumers' stocks. Withdrawals from producers' stocks totaled 31,443 short tons in 1939, and 30,188 in 1940; additions to producers' stocks totaled 56,479 tons in 1938, 12,232 in 1941, and 5,502 in 1942.
 Based upon average price of primary aluminum as reported to Bureau of Mines.
 Crude and semicrude, some of which may be secondary aluminum.
 Shipments

Of the primary and secondary aluminum consumed in the form of fabricated products, about 60 percent went into airplane construction in airframes, landing gear, engines, propellers, and fittings. greater part of the remainder was used in ship construction, tank engines, ordnance, and other military uses. Only a minimum of civilian needs, such as tools, some chemical equipment, and deoxidation in steel manufacture, were filled. Prewar uses of the metal, such as automobiles, trains, electrical conductors, furniture, household utensils, decorations, packaging, and bridge and building construction, have been virtually eliminated for the duration of the war.

Consumption of aluminum in 1943 will follow a pattern similar to that in 1942, but over-all consumption is expected to be nearly twice Aircraft construction, which may reach 100,000 planes in 1943, will continue to demand the largest share of the available supply; Army, Navy, and Lend-Lease requirements will take most of the remainder; and indirect military and essential civilian consumption is expected to be allotted only about 8 percent of the total.

### PRICES

Throughout 1942 the New York open-market base price of primary aluminum remained at 15 cents a pound for lots of 10,000 pounds or more, 99 percent plus pure ingot aluminum, delivered. Deductions allowed for transportation charges on orders of 500 pounds or more cannot exceed the lowest carload rate of rail freight. On December 5, 1942, the Aluminum Co. of America for the first time in recent years included pig aluminum in its price schedule. The price was set at 14 cents a pound for guaranteed 99 percent average minimum purity and is subject to the same transportation deductions as primary ingot.

Prices of fabricated and semifabricated products have been reduced substantially since the beginning of 1942. These reductions are attributed to mass production, manufacturing improvements, lowered operating costs, and continued research.

Price schedule No. 2, Aluminum Scrap and Secondary Ingot, was originally issued and effective March 24, 1941. During 1942 a total of 12 price actions was taken with respect to this schedule,

which was reissued effective February 17,1942, embodying all previous amendments. Since that date, sales of idle inventories to Metals Reserve Co. at the order of the War Production Board have been exempt from the order; prices have been set on additional grades of scrap; all grades of obsolete scrap except pure cable have been reduced in price; payment for contaminated aluminum-containing




FIGURE 2.—Trends in production, imports and exports, apparent consumption, and average quoted prices of aluminum, 1913-42. Price is for No. 1 virgin 98-99 percent at New York through 1929, thereafter for 99-percent-plus virgin ingot, as reported by American Metal Market.

material has been limited to the actual metal contained; and a maximum price has been set for aluminum-bearing materials. On November 11, 1942, the Office of Price Administration announced that a premium of one-half cent a pound would be allowed in baled or packaged scrap sales to primary producers and 1 cent a pound for

briquetted scrap. On January 5, 1943, the Office of Price Administration announced the establishment of a maximum base price of 15 cents a pound for secondary ingot, and lower prices were set for lowgrade alloys. The effect of this amendment was to rearrange and simplify the former classification of secondary ingot, and it had only a slight effect on prices.

#### FOREIGN TRADE

Imports and exports of crude and semicrude aluminum in 1942 were 736 and 419 percent more, respectively, than in 1941. The value of imports and exports of manufactured aluminum products increased 870 and 291 percent, respectively. Imports, exclusive of scrap, constituted 19 percent of the apparent consumption of primary aluminum in 1942. Of the imports of crude (105,795 short tons), less than 1 ton came from Curação and the remainder from Canada; of semicrude (5,855 tons), 5,799 tons came from Canada, 56 tons from Mexico, and less than 1 ton from other countries; and of scrap (487 tons), 464 tons came from Canada, 3 from Iceland, 2 from Panama, 8 from Canal Zone, 2 from Peru, 3 from New Zealand, 5 from Mexico, and less than 1 ton each from Curação, Cuba, Haiti, Venezuela, Chile, British East Africa, and the Bahamas.

Of the crude aluminum exported in 1942 (17,834 short tons), 439 tons went to Canada, 2 to Argentina, 1,704 to the United Kingdom, 4 to Australia, 111 to Brazil, 15,566 to U. S. S. R., 2 to India, 5 to China, 1 each to Chile and Surinam, and less than 1 ton to Canal Zone, Peru, and Egypt; of semicrude (20,898 tons), 3,715 tons went to the United Kingdom, 12,162 to U. S. S. R., and 5,021 to other countries; and of scrap (32 tons), all went to Canada.

Aluminum imported for consumption in the United States, 1940-42, by classes

	1940		1941		1942	
Class	Short tons	Value	Short tons	Value	Short tons	Value
Crude and semicrude: Metal and alloys, crude Scrap Plates, sheets, bars, etc	17, 435 648 1	\$4, 628, 601 108, 035 592	12, 830 55 528	\$3, 333, 642 13, 440 271, 675	105, 795 487 5, 855	\$33, 148, 393 131, 142 2, 204, 331
•	18, 084	4, 737, 228	13, 413	3, 618, 757	112, 137	35, 483, 866
Manufactures: Leaf (5½ by 5½ inches) Powder in leaf (5½ by 5½ inches) inches)	(1)	12, 138	(¹) (²)	14, 825 74		
·Bronze powder and pow- dered foil			22	28, 044	(3)	4
Foil less than 0.006 inch thick Table, kitchen, hospital	471	389, 868	117	110, 166	(3)	37
utensils, etcOther manufactures	(4) 4	5, 149 15, 541	(4) 2	3, 620 52, 057	(3) (4)	91 1, 639, 659
	(4)	422, 696	(4)	208, 786	(4)	1, 639, 791
Grand total	(4)	5, 159, 924	(4)	3, 827, 543	(4)	37, 123, 657

<sup>1 1940: 10,244,034</sup> leaves; 1941: 11,113,500 leaves; equivalent in pounds not recorded.
2 1941: 50,000 leaves; equivalent in pounds not recorded.
3 Less than 1 ton.

<sup>4</sup> Quantity not recorded.

は かん かんなん 大学 日本

Aluminum exported from the United States, 1940-42, by classes

	1940		1941		1942	
Class	Short tons	Value	Short tons	Value	Short tons	Value
Crude and semicrude:						
Ingots, slabs, and crude Scrap Plates, sheets, bars, etc	12, 227 955 14, 659	\$5, 352, 151 331, 757 12, 235, 124	750 57 6, 655	\$325, 218 22, 352 4, 445, 018	17, 834 32 20, 898	\$5, 514, 562 1, 157 14, 024, 022
	27, 841	17, 919, 032	7, 462	4, 792, 588	38, 764	19, 539, 741
Manufactures: Tubes, moldings, or other shapes	1, 233	1, 273, 793	367	550, 606	3, 392	5, 390, 267
Table, kitchen, and hos- pital utensils Foil Powders and pastes (alu-	421 1, 404	482, 869 1, 221, 590	298 274	281, 851 246, 259	138 129	161, 806 121, 800
minum and aluminum bronze)Other manufactures	(²)	370, 061 1, 169, 780	1 239 (2)	206, 776 794, 442	1 1, 313 (2)	651, 802 1, 000, 028
	(2)	4, 518, 093	(2)	2, 079, 934	(2)	7, 325, 703
Grand total	(2)	22, 437, 125	(2)	6, 872, 522	(2)	26, 865, 444

# TECHNOLOGIC DEVELOPMENTS

One of the most important technologic advances of 1942 was the development of the lime-soda-sinter method for treating red mud tailings from the Bayer process. Lime-soda-sinter units are being constructed at the four Aluminum Co. of America alumina plants at Mobile, Ala., Baton Rouge, La., Hurricane Creek, Ark., and East St. Louis, Ill., and will operate in conjunction with the Bayer plants by a combination process developed in pilot-plant experimentation at East St. Louis. High-silica bauxite will be treated directly by the Bayer process, and the red mud tailings will be sintered with lime and soda ash in rotary kilns. The sintered material will be leached, and the sodium aluminate liquor thus obtained will be added to the Bayer liquors. No increase in alumina capacity is to be expected from this process; it is solely a means of extracting a larger percentage of alumina from high-silica bauxites than is possible by the Bayer method.

Much research was carried out in 1942 and early 1943 on the problem of obtaining alumina from clay and other materials. Kalunite, Inc., in its pilot plant at Salt Lake City has further developed and perfected its process for the production of alumina from Marysvale (Utah) alunite. By this process the alunite is crushed, roasted, and dissolved in sulfuric acid, after which the basic alum, formed by decomposition of crystallized potash alum, is sintered. The sintered product is leached, leaving the insoluble alumina behind.

Investigations and research on the extraction of alumina from clay, low-grade bauxite, and alunite, and on the beneficiation of aluminous ores are being carried out by the Bureau of Mines in its laboratories and pilot plants at Tuscaloosa, Ala.; Rolla, Mo.; Salt Lake City, Utah; Boulder City, Nev.; College Park, Md.; Norris, Tenn.; and Seattle, Wash.

Aluminum content.
Quantity not recorded.

The presence of minor alloying elements commonly found as impurities in aluminum was studied with respect to the allowable limits of impurities and their effect on the physical properties of aluminum casting alloys.2 Continued expansion in capacity and number of sand casting foundries resulted in improved foundry techniques and greater output.3 Advancement in plating on aluminum as the base material was marked in 1942,4 and studies were made on the electrodeposition of aluminum on other metals.<sup>5</sup> cleaning and finishing of aluminum used on warplanes received much attention. Improved alloying technique and numerous patents for new alloys accompanied the expansion of fabricating facilities.7 The Aircraft Parts Division of the Reynolds Metals Co. is producing finished aircraft parts at its Louisville, Ky., plant and shipping them direct to aircraft manufacturers, thereby greatly reducing the usual 3- to 6-month delay in scrap return when sheet instead of finished parts is shipped.8

Anhydrous aluminum sulfate can be produced from commercial aluminum sulfate by a process that avoids the mechanical difficulties caused by transformation of the salt through a fluid, sticky stage previously considered unavoidable (U.S. Patent 2,304,519). A new process has been developed for the production of an aluminum chloride catalyst by soaking pieces of a suitable carrier material in a bath of molten anhydrous aluminum chloride (U. S. Patent 2,295,977).

# WAR MEASURES

Mandatory priorities restricting delivery, processing, use, and inventories, which had been placed on aluminum by the Office of Production Management on March 22, 1941, were kept in force throughout 1941 and 1942. The original order, M-1, was changed and revised by the War Production Board. The order in force on April 1, 1943, was M-1-i, effective August 18, 1942, and last amended November 20, 1942; it provides for complete allocation control of virgin and secondary metal.

Order M-1-d, covering aluminum scrap containing more than 15 percent aluminum, became effective January 7, 1942, and prohibits the use of scrap, except home scrap, without the authority of the Director of Industry Operations. The order does not apply to virginaluminum producers or approved smelters. Each plant generating 1,000 pounds or more of scrap must segregate scrap at the machine and all 17S, 24S, and 52S alloy scrap in solid form must be sold to Aluminum Co. of America or Reynolds Metals Co. Other segregated scrap must be sold to these companies or approved dealers and smelters and the identity of segregated scrap must be certified to by the seller.

Manufacture and sale of aluminum pigments and paints was prohibited by order M-1-g effective March 10, 1942.

<sup>&</sup>lt;sup>2</sup> Bonsack, Walter, Effects of Minor Alloying Elements in Aluminum Casting Alloys: Iron Age, vol. 150, No. 7, August 13, 1942, pp. 68-74.

<sup>3</sup> Allen, Arthur H., Buick Speeds Production of Aluminum Alloy: Foundry, vol. 70, No. 12, December 1942, pp. 66-71, 150-153.

<sup>4</sup> Yates, Raymond F., Plating on Aluminum: Metals and Alloys, vol. 16, No. 6, December 1942, pp. 1084-1088.

Ostrow, B. D., A Résumé on the Electrodeposition of Aluminum: Metal Finishing, February 1943,

pp. 70-72.

6 Faulhaber, Frank V., Finishing Warplanes: Metal Finishing, vol. 41, No. 2, February 1943, pp. 113-119.

7 Robinson, J. Towns, Development of Aluminum Alloys: Metallurgia, vol. 27, No. 158, December 1942,

pp. 41-44.

\* Froelich, M. H., Producing Aircraft Parts at the Aluminum Mill: Aero Digest, vol. 42, No. 1, January 1943, pp. 104, 109-110, 113-114.

できるとことのなるというとうないとうと

On August 1, 1942, order M-1-h, fully allocating bauxite and alumina, became effective. For the purpose of this order bauxite was defined as "restricted" and "nonrestricted." Restricted bauxite (containing less than 15 percent silica) was further subdivided into high-silica restricted (8 to 15 percent silica) and low-silica restricted (less than 8 percent silica). The purpose of the order is to make certain that the higher grades of ore are allocated to the most essential needs and that no user who can use nonrestricted ore receives any of the high-grade material. Alumina and primary alumina products are stringently controlled by the order in an effort to divert all possible calcined alumina to the aluminum industry and essential abrasive uses, and small quantities of primary alumina products are manufactured and allocated to essential uses, largely refractories, catalysts, and the production of certain chemical products.

On November 2, 1942, the War Production Board announced a new long-range plan for controlling the flow of critical materials into war uses—the widely heralded Controlled Materials Plan. Under it, requirements for critical materials will be adjusted to the available supply, and the quantity and type of materials required will be available at the time and place necessary to meet approved programs. The plan, in effect a vertical allotment system, was applied to the three most basic and critical materials—aluminum, copper, and steel—and became effective in its transitory stages in the second quarter of 1943. The former horizontal allotment system—the Production Requirements Plan—will be completely replaced by the Controlled Materials Plan by July 1, 1943, for the above-mentioned critical materials.

# WORLD BAUXITE AND ALUMINUM INDUSTRIES

Production and consumption of aluminum reached an unprecedented record in 1942, and this high mark will be considerably exceeded in 1943; most of the increase will be from expanded facilities in North America.

World production of bauxite, 1938-42, by countries, in metric tons

[Compiled by B. B. Waldbauer] 1942 1938 1939 1940 1941 Country (1) 820 ~79 New South Wales
Victoria
Brazil (exports) (1) 1,000 442 3 4, 000 <sup>1</sup>, 000 14, 365 (1) 1700, 000 225, 000 15, 000 12, 928 (1) 682, 440 19, 703 12, 397 18, 279 12, 397 (1) 2 650, 000 2 25, 000 2 45, 000 3 50, 000 (1) 2 700, 000 2 20, 000 2 800, 000 2 20, 000 Czechoslovakia.... Germany Gold Coast <sup>(1)</sup> <sup>2</sup> 50, 000 179, 886 186, 906 Guiana: 21,175,000 21,245,000 21,200,000 30,000 21,000 2100,000 2400,000 275,000 2 700, 000 615, 434 2 647, 000 2 15, 000 118 1, 089, 833 1, 198, 900 21, 000, 000 225, 000 21, 000 382, 409 377, 213 540, 718 British...... Netherlands (Surinam)..... 483, 653 511, 619 485, 000 9, 121 330 Hungary..... India, British. 15, 005 160 Indochina..... 21,000 240,000 2600,000 171,821 21,000 240,000 21,000 (1) 275,000 <sup>(1)</sup> <sup>2</sup> 530, 000 Ireland Italy Japan Netherlands Indies 483, 965 2 39, 000 230, 668 180 360, 837 3 43, 000 274, 345 1, 030 20,000 245,354 160,000 1,000 Portuguese East Africa... <sup>2</sup> 40, 000 11,807 10, 460 2 40, 000 1,000 Southern Rhodesia (1) 75, 000 271 55, 965 2 250, 000 315, 906 396, 368 93, 737 2 270, 000 381, 331 318, 840 63, 787 2 300, 000 445, 958 2 290, 000 Unfederated Malay States: Johore..... 250,000 908,525 2400,000 275, 000 2, 511, 385 200, 000 U. S. S. R. United States (dried-bauxite equivalent)... 8, 276, 000 3, 869, 000 4, 344, 000 4, 737, 000 6, 657, 000

Data not available.
 Estimated production. Estimates for 1939, 1940, 1941, and 1942, by the authors.

World production of aluminum, 1938-42, by countries, in metric tons
[Compiled by B. B. Waldbauer]

Country	1938	1939	1940	1941	1942
Canada	66, 000	75, 000	1 100, 000	1 200, 000	1 300, 000
France Germany	45, 300 161, 100	50,000	1 59, 000	1 62, 200	1 70, 000
Austria	4, 500	210,000	1 240, 000	1 300, 000	1 350, 000
Hungary India	1, 500	1, 500	1 2, 800	1 5, 000	1 5, 000 1 500
Italy	25, 800	34, 200	1 40, 000	1 50, 000	1 45, 000
Japan	17,000	23, 000	1 35, 000	1 65, 000	1 90, 000
Norway	29,000	31,000	1 28, 000	1 18, 000	1 22, 000
Spain	651	1 800	271	1 700	1 800
Sweden	2, 400	2, 700	1 2, 000	1 2, 500	1 2, 000
Switzerland	27, 000	28,000	1 31, 000	1 25, 000	1 25, 000
U. S. S. R	43, 800	1 73, 000	1 75, 000	1 55, 000	1 55, 000
United Kingdom United States	23, 300	25,000	1 28, 000	1 35, 000 280, 383	1 50, 000 472, 737
Yugoslavia	130, 100 1, 200	148, 400 2, 400	187, 100 1 2, 800	1 3, 000	1 3, 000
	578, 700	705, 000	831, 000	1, 101, 800	1, 491, 000

<sup>1</sup> Estimated production. Estimates for 1939, 1940, 1941, and 1942 by the authors.

World production of bauxite is estimated to have reached approximately 8,276,000 metric tons in 1942, 24 percent more than in 1941 and 114 percent more than in the pre-war year 1938. Of the world output in 1942, it is thought that the production in Axis dominated or controlled territories was 2,876,000 tons or 35 percent and that 5,400,000 tons or 65 percent was under United Nations control.

The aluminum produced in 1942 is estimated to have totaled 1,491,000 metric tons, 35 percent more than in 1941 and 158 percent more than in 1938. Of the world output in 1942, it is thought that production under the control or domination of the Axis in Europe and the Far East was 612,800 tons, or 41 percent, and under total United Nations control 878,200 tons, or 59 percent.

#### REVIEW BY COUNTRIES

Australia.—Bauxite is mined at Bundanoon, New South Wales, for use as a flux in steel manufacturing by Broken Hills Proprietary, Ltd., and at Nahoo and Boolara, Victoria, for chemical purposes and alumina production by Sulphates, Ltd., at Melbourne. According to present plans the production of bauxite will not exceed 5,000 tons in 1943. Sulphates, Ltd., the only producer of alumina in the Commonwealth, has a plant of 1,000 tons annual capacity and successfully uses a sodium bisulfate process developed by Michael Martin as an improvement on the Penniakoff process. It is reported that an acid process using ammonium sulfate is under consideration in plans for a possible expansion of alumina capacity. Proposals to erect a reduction plant at Sydney apparently have not yet materialized and may have to wait until after the war. Fabricating facilities have been greatly expanded, and it is reported that consumption of ingot has nearly doubled.

Brazil.—Construction has been nearly completed on the 10,000-ton alumina plant and 2,000-ton reduction plant of the Companhia Electro-Chimica Brasileira at Saramenha, near Ouro Preto, Minas Gerais. These plants will be able to fill present Brazilian domestic needs for alumina and aluminum. The Gambe deposit near Ouro Preto with a 2,000,000-metric ton reserve will supply the alumina

plant with ample high-grade material. Negotiations have been continuing between Brazil and the United States to obtain equipment for mining the Pocos de Caldas deposits and for the construction of a 40,000-ton alumina plant and a 20,000-ton reduction plant near São Paulo. The bauxite deposits on the Pocos de Caldas Plateau are said to contain 7,000,000 tons of proved reserves. Estimates by the Brazilian Government indicate 120,000,000 tons of possible ore. Analyses of the bauxite range from 57 to 61 percent Al<sub>2</sub>O<sub>3</sub>, according to a reliable source. Power for the reduction plant would be obtained from standby power from the São Paulo Tramway Light & Power Co. at Serra Cubatao and from two additional units to be constructed. Exports of bauxite from Brazil in 1942 totaled 12,397 metric tons compared with 14,365 tons in 1941.

British Guiana.—Exports of bauxite by the Demerara Bauxite Co., Ltd., and the Berbice Co., Ltd., totaled 1,116,463 long tons in 1942, of which 872,138 tons went to Canada, 204,750 to the United States, 39,574 to the United Kingdom, and 1 to Trinidad. The Berbice Co., Ltd., began sending dried bauxite by barge from its property 130 miles up the Berbice River to the loading point of Everton in the early spring of 1942 for shipment to Canada. This company has been shipping bauxite solely to Canada. The Demerara Bauxite Co., Ltd., is reported to have opened up a new deposit of bauxite 40 miles up river from the port of MacKenzie. The Demerara River was being dredged in late 1942 to facilitate transport of ore by allowing deeper

draught vessels to load farther upstream.

Canada.—Compared with 1942, Canadian aluminum production is expected to increase more than 50 percent in 1943. The estimated rate of production to be attained in 1943 is 508,000 tons. The gigantic facilities of the Aluminum Co. of Canada for alumina and aluminum at Arvida, Quebec (1,050,000-ton alumina plant and 360,000-ton reduction plant) are by far the largest in the world and at capacity will supply nearly one-fourth of the metal to be produced annually in the Western Hemisphere. Other Canadian reduction plants, all owned by the Aluminum Co. of Canada, are at Shawinigan Falls (75,000 tons capacity), Beauharnois (25,000 tons capacity), Le Touque (25,000 tons capacity), and Isle Maligne (15,000 tons capacity). With the exception of one potline at Isle Maligne all the above plants were in full operation on May 1, 1943. A lime-soda-sinter plant will be completed in the third quarter of 1943 at Arvida for use in conjunction with the present Bayer facilities if the shipping situation should deteriorate further and necessitate the importation of relatively highsilica Arkansas bauxite from the United States. Since 1939 aluminumfabricating facilities have been greatly expanded, principally at Kingston, Ontario, where strong-alloy sheet, extrusions, and forgings are made, partly for United States consumption. Rolled screw machine and rivet stock is produced at Shawinigan Falls, Quebec, and sheet and castings at Toronto, Ontario. At Toronto a new sand-casting foundry is producing 200,000 pounds of castings a month. The Kingston forging plant is turning out 10,000 propeller blades a month, most of which are for the United States.

To save shipping space bauxite cargoes from British Guiana and Surinam were unloaded largely at eastern United States ports, principally New York, and then shipped by rail or rail and barge to the

alumina plant at Arvida.

Central America.—Bauxite deposits have been reported from Nicaragua, Honduras, and El Salvador. No definite information is available on grade or reserves, but exploration is being pressed.

China.—Large deposits of aluminous material have been discovered in western China in the Provinces of Yunnan and Szechwan. It is reported that exploitation will be undertaken by the Chinese Economic Ministry.

Colombia.—A deposit of bauxite has been reported in the region of

San Martin, Intendencia del Meta.

France.—French aluminum production in 1941 was only 62,200 tons, falling short of its objective of 70,000 tons by about 10 percent. Fuel, power, and rail shortages probably were the primary causes, aided by labor shortages and labor troubles. Production in the first quarter of 1942 is reported to have been at a rate slightly exceeding 70,000 tons. The well-known French firm of Alais, Froges & Camargue (Pechiney) is understood to have expanded its capacity by constructing two new plants at the suggestion of the Germans. The company capital was doubled to more than 800,000,000 French francs to make the expansion possible. During 1942 alumina was exported to Germany, and there is reason to believe that a substantial share of this was reshipped to Norway. According to Vichy several hundred French prisoners of war were sent back from Germany to work in the bauxite mines in the

Brignoles area.

Germany.—German and Austrian aluminum production in 1942 has been estimated at 350,000 tons. Larger production, desperately needed to supply the Luftwaffe with planes, is thought to have been retarded by shortages of power, labor, and transportation. power stations supplying electric energy for the aluminum plants are mostly based on lignite; labor for lignite mining and transport for bauxite seem to be the principal limiting factors in the German aluminum industry. Reports indicate that most German bauxite imports are from Hungary and southern France since transportation from these sources is easier than from the more remote bauxite districts of Croatia, Italy, and Greece. Intense effort is being put forth to recover all possible light-metal scrap, and remelters have been instructed to concentrate on 14 grades of remelted aluminum. of these grades are blended with virgin ingot for use, but some are sold direct to foundries by the Association of German Aluminum Smelting Works.

Gold Coast.—Deposits in the Gold Coast became one of the major sources of bauxite for the United Kingdom aluminum industry in 1942. Development is progressing rapidly, and it is hoped that 120,000 tons of ore will be produced in 1943. Plans are to increase annual production to 240,000 tons by the end of 1945. All bauxite being produced at present is from the Sefwi Bekwai area in the western province of the Colony. Britain wishes to obtain rolling stock and mining equipment from the United States to facilitate shipping and increase

the capacity of the mines.

Major deposits of bauxite in the Gold Coast are the following: Yenahia group, Ashanti, where reserves, including highly ferruginous bauxite, are estimated at 168,000,000 tons, some of which analyzes 1 percent SiO<sub>2</sub> and 63 percent Al<sub>2</sub>O<sub>3</sub> and is 20 feet thick; Affoh group, Sefwi Bekwai, with estimated usable reserves of 32,130,000 tons; Asafo, N. W. Sefwi, 5 miles north of Asempanaiye, where 15,000,000 tons average more than 55 percent Al<sub>2</sub>O<sub>3</sub>; and Mount Ejuanema,

THE REPORT OF THE PARTY OF THE

Kwaho, 2 miles from the railhead at Nkawkaw and 112 rail miles from the port of Accra, with estimated reserves of 4,000,000 tons of massive and rubbly bauxite. Numerous other minor deposits are scattered throughout the country and occur mainly as cappings of aluminous laterite on flat-topped hills. High-grade chemical ore exists in the Gold Coast to some small extent, but on the average the bauxite found here is comparatively low in silica and high in iron.

Tremendous tonnages of metallurgical ore are available.

Hungary.—According to recent reports the world's richest bauxite deposits have been discovered in the mountain region of Borzoeny, Hungary. No statement of the size of this deposit has been made. but before its announcement bauxite reserves in Hungary had been estimated at 250,000,000 tons. The deposits of the Vertesgebirge alone contain 120,000,000 tons and are mined by open-cut methods. Operating companies in this area are members of Bauxit Trust A. G., Zurich, and export most of the production to Germany. The small quantity used domestically is consumed by the alumina plant of the Bauxite Industry Co., a subsidiary of Bauxit Trust A. G., which supplies the 3,000-ton reduction plant at Csepel and the 2,000-ton reduction plant of the Hungarian General Coal Mining Co. at Tatabanya. Bauxit Trust A. G., in 1942 established a Hungarian subsidiary, Donautaler Tonerdeindustrie A. G., to produce alumina near one of the existing reduction plants. The capital of the new company, 35,000,000 pengo, is divided between the Hungarian state, Bauxit Trust A. G., and Aluminium Werke A. G., Berlin. Ungarische Bauxitgruben A. G. has started to construct its 20,000-ton alumina and 10,000-ton reduction plant at Ajka near Veszprem. To ensure sufficient power for these plants a power unit producing 250,000,000 kw.-hr. a year was erected. This expansion will cover domestic requirements of the metal and will leave a balance for export to other European countries without greatly affecting bauxite exports. extent to which the Hungarian aluminum industry can be expanded depends on power sources. Since the return of northern Translyvania to Hungary, plans are said to be proceeding for generating more hydroelectric power in the Carpathians.

India.—Titaniferous bauxite has been located in Jashpur State, Chota Nagpur, India. The deposits, however, are far from rail facilities, and the nearest important town—Ranchi—is 100 miles Exploration has continued on the bauxite deposits in the Shevaroy Hills in Madras. The Aluminium Corporation of India, Ltd., an Indian-owned company, has a 6,000-ton alumina plant at Anupuagar near Asansol; bauxite deposits are nearby. A reduction plant was also started there several years ago, but owing to shortages of material it probably cannot be completed until after the war. Alumina production ceased after the production of 60 tons, and there appears to be no present prospect of its being resumed. minium Production Co. of India, Ltd., part British- and part Canadianowned, has constructed a reduction plant at Alwaye, Travancore, which is reportedly producing at the rate of 1,500 tons annually. Capacity will be nearly doubled when additional power facilities have been installed. Alumina for the plant is being supplied from a prewar stock pile which appears to be running low. Efforts to bring the alumina plant at Anupuagar back into production have been unsuccess-The Aluminium Production Co. of India, Ltd., also owns and operates a fabricating plant at Calcutta which, with small additions,

can turn out 2 million pounds of strong alloy sheet a year. The

necessary equipment will be installed by October 1943.

Ireland.—It is estimated that 100,000 tons of bauxite were shipped to Britain from Ireland in 1942. Bauxite occurs in commercial quantities in County Antrim in northeastern Ireland, where it is found in lenticles and irregular masses between two basaltic flows. The individual deposits appear to have no great extent or thickness.

Italy.—The alumina and aluminum facilities of Italy are extremely vulnerable to Allied air attacks since the last Axis forces have been swept from Tunisia. It is not unlikely that the Italian light-metal industries will be greatly impaired by Allied air activities, if indeed they have not already been seriously disrupted. The following list gives the location of the alumina and aluminum plants:

or	npany: fall office and fall of the little		Alumina	Aluminum
	Ind. Nazionale Alluminio	Porto	Marghera	Bolzano.
		Bolza	no	
	Societa Italiano Allumina	Porto	Marghera	
M,	Societa Ind. Min. El. Chim. (S. I. M. E.)	Bussi		
	Societa Alluminio Veneto Anonima	Porto	Marghera	Porto Marghera.
,	(S. A. V. A.).			an is said a saide a said
	Societa Nazionale Alluminio			Mori.
1	Societa Alluminio Italiano			Borgofranco.

Two more reduction works have been proposed—at Ferrara and Manteca.

Jamaica.—Extensive deposits of low-silica, high-iron bauxite were discovered in Jamaica in the latter half of 1942. Preliminary estimates indicate that over 10,000,000 tons of ore are available in small deposits of 30,000 to 60,000 tons each. The deposits occur as parts of an unconsolidated mantle overlying Tertiary limestone of probable Oligocene age and are found in two general areas—the first 15 miles northwest of Old Harbor and the second 20 miles north of Kingston. Overburden is said to be light or absent over much of the Analyses indicate the following composition of the bauxite: 46 to 49 percent Al<sub>2</sub>O<sub>3</sub>, 1 to 3 percent SiO<sub>2</sub>, and 15 to 20 percent Fe<sub>2</sub>O<sub>3</sub>. The deposits are said to be accessible by rail and motor road to deep water harbors. The Government has decreed under the Defense Regulations that any bauxite or other minerals worked on the island shall become the property of the King and disposed of in accordance with Government regulations. Canada is reported to be planning to import 500,000 tons from this source in 1943 if the deposits can be put into operation soon enough and if certain technical difficulties involving the high iron content can be solved.

Japan.—No official information is available on activity in the alumina and aluminum industries during 1942. Japan's goal in her Four-Year Plan for light-metal production was reported to have been 140,000 to 150,000 metric tons. Present information indicates that this goal was revised downward considerably, and 1942 production is estimated at 90,000 metric tons. Japan has ample reserves of bauxite at her command in the Netherlands East Indies on Bintan Island, Johore, and the Japanese-mandated Caroline Islands. Plans were to import 50,000 tons of high-grade bauxite from the Caroline Islands in 1941 and to step up the import rate from Johore, Unfederated Malay States (75,000 tons estimated for 1941). According to German reports deposits of aluminous material in Korea, Formosa, and Manchuria will be developed by the Japanese light-metal industry.

Deposits estimated at 10,000,000 tons in the Japanese-mandated Caroline Islands (Palao, Panope, Yap, Marakaro, and Garasumao)

have been developed by the Nanyo Aluminium Industry Co., a subsidiary of the Japanese South Seas Development Co. The ore averages 55 percent Al<sub>2</sub>O<sub>3</sub>, 1 percent SiO<sub>2</sub>, and 11 percent Fe<sub>2</sub>O<sub>3</sub>.

Liberia.—The chief deposits of bauxite noted are in the Bulcama and Gisima Sections of the Lorma or Buzi country, at Massao, between

Kpaia and Zorzor and between Zorzor and Pisabu.

Netherlands East Indies.—Bauxite produced on the island of Bintan opposite Singapore and the neighboring islands of Angkoet and Kojang has been under the control of the Japanese since early 1942. Deposits estimated at 10,000,000 to 20,000,000 tons had been developed by the Nederlandische Indische Bauxiet Exploitatie Maatschappij on these islands, averaging about 54 percent Al<sub>2</sub>O<sub>3</sub>, 2 to 3 percent SiO<sub>2</sub>, and 13 percent Fe<sub>2</sub>O<sub>3</sub>. The principal workings are at Soengi Kolak on the Kidjang Strait. Before Japanese occupation, the bulk of the production since 1939 had been exported to Japan. It is estimated that, when fully exploited, the deposits of the Netherlands East Indies can supply the Japanese aluminum industry with

400,000 tons of bauxite annually.

Norway.—Before the German occupation of Norway, six plants with a total capacity of 22,000 tons of alumina and 36,000 tons of aluminum were in operation. Rated annual capacities of the reduction plants were as follows: Stangfjord (owned by British Aluminium Co.), 800 tons; Vigolands Brug (owned by British Aluminium Co.), 3,500; Eydehavn (owned by Det. Norske Nitrid A. S.), 9,500; Hoyanger (owned by Norske Aluminium Co.), 8,000; Haugvik (Glomfjord) (owned by International Aluminium Co.), 9,000. Alumina capacity was concentrated at the Hoyanger plant which had a 22,000-ton rated annual capacity. Norwegian aluminum production was to have been raised to approximately 130,000 tons through German controlled and financed expansions, but latest indications are that numerous difficulties have appeared to greatly impede this plan. Not the least of the troubles experienced by the Germans has been the vexing problem of supplying Norway with bauxite and alumina from France, Hungary, and Germany. Swedish information indicates that some of the aluminum works have been closed by the Germans because of the raw material situation. Reports of sabotage of German equipment for the reduction plants and alumina plants are numerous and suggest another reason for German retrenchment in the expansion

Spain.—A new aluminum plant with an annual capacity of 8,000 tons will be built by Empresa Electro-Mecanica de Cordoba, in Spain. At present Aluminio Español at Sabinania with an annual peak capacity of 1,100 metric tons is the only light metal producer in this country. Production at Aluminio Español remained at only about

70 percent of capacity during 1942 owing to a power shortage.

Surinam.—Virtually all of the 1,150,000 long tons of bauxite exported from Surinam (Netherlands Guiana) in 1942 by the Surinamsche Bauxite Maatschappij (subsidiary of Aluminum Co. of America) and the N. V. Billiton Maatschappij went to the United

States and Canada.

Sweden.—The A. B. Svenska Aluminium Kompaniet, which raised its capital in 1941 to 2,000,000 Swedish kronor, has been granted a Government credit of 1,000,000 kronor to finance expansions of its works. Importation of alumina from Norway to the Mansbo reduction works near Avesta was stopped in 1941; to meet the alumina

shortage a subsidiary, A. B. Svenska Aloxidverken, was formed and has constructed a plant at Kubikenborg near Sundsvall for the manufacture of alumina from andalusite. This plant began operation in the spring of 1942; the capacity, estimated at 6,000 tons a year, can be increased if necessary.

Switzerland.—Owing to an acute shortage of copper Switzerland has had to rely more and more on aluminum as a substitute, particularly for electrical purposes. This has resulted in a 50-percent cut in the exports of aluminum and a drastic series of regulations on the domestic use of the metal, especially in containers, furniture, cooking utensils,

and luxury items.

Unfederated Malay States: Johore.—The principal bauxite deposits in Malaya now under Japanese domination are in South and West Johore. Deposits have been developed at Bukit Pasir and Sri Medan, near Batu Pahat, by the Japanese Ishihare Sangyo K. K. and at Perigi Achih, 12 miles east of Johore Bahru, by Chinese enterprise. The ore is said to average 52 to 61 percent Al<sub>2</sub>O<sub>3</sub>, 5 to 15 percent Fe<sub>2</sub>O<sub>3</sub>, and 2 to 7 percent SiO<sub>2</sub>. Ports of shipment for the bauxite are at Batu Pahat and Penggarand. Virtually the entire output has been shipped to Japan since the opening of the mines in 1936.

United Kingdom.—It is estimated that British aluminum production in 1942 increased about 40 percent over that in 1941. The bulk of British requirements, however, continue to be filled largely from Canada. The Open General License permitting the importation of bauxite and cryolite into the United Kingdom has been revoked by the Board of Trade; separate licenses were required for goods dispatched to the United Kingdom after November 9, 1942, and imported into the United Kingdom after January 9, 1943. Prices of 99 percent ingot

remained pegged at £110 a ton delivered.

Yugoslavia.—Bauxite production in Dalmatia and Hercegovina is reported to have declined from 270,000 tons in the first 6 months of 1941 to 106,000 tons in the same period of 1942. The Croatian Aluminum Co. has been formed in Agram with a capital of 20,000,000 kroner to erect an alumina plant with an annual capacity of 100,000 tons and a reduction plant with a 50,000-ton annual capacity near Hum, Hercegovina. Domestic bauxite will be furnished from large deposits in the Karst region of Dalmatia and Hercegovina where bauxite containing 54 to 60 percent Al<sub>2</sub>O<sub>3</sub> and 1 to 2 percent SiO<sub>2</sub> is reported to occur in large quantities.

# **MERCURY**

By H. M. MEYER AND A. W. MITCHELL

#### SUMMARY OUTLINE

	Page		Pag
Summary	713	Prices	71
Salient statistics	714	Prices. Consumption	71
Office of Price Administration	714	Stocks	71
Metals Reserve Co	714	Review by States	72
Consumption restrictions	714	Foreign trade	72
Bureau of Mines and Geological Survey		World production	72
activities	714		
Tests for mercury	716		1

## SUMMARY

The year 1942 marked continuation of the forward movement of mercury production in the Western Hemisphere. The output of 50,846 flasks in the United States is the highest since 1882 and has been surpassed in only eight previous years. Mexico and Canada established new peak rates by substantial margins, Chile and Peru likewise contributed to the total, and development was under way in other areas. Mexico's output was 32,443 flasks compared with the previous record of 23,137 flasks in 1941, and Canada's totals were 13,470 and 7,057 flasks, respectively. As pointed out in previous issues of Minerals Yearbook, developments in Western Hemisphere sources since the war began have exceeded expectations and, coupled with restrictive consumption measures, have solved United Nations problems with regard to this strategic metal.

Reports emanating from Italy and Spain, normally the principal mercury-producing nations, indicate that those countries also attained record output. These claims cannot be verified, and it does not seem entirely reasonable to suppose that they are true in view of the curtailed world markets available to the two countries. On the other hand, stocks in Spain are reported to have gained sharply; if this report is reliable, it would tend to confirm the claim of high production rates. If actually establishing production records, Spain and Italy together could readily be recovering over 140,000 flasks of mercury

annually.

Despite conservation measures, consumption in the United States was again higher than in any other year, surpassing the previous record (that in 1941) by 11 percent. Domestic production for the year could slightly more than take care of domestic needs, but requirements in the second half of the year exceeded production by 7 percent.

Under arrangements made by the Metals Reserve Co., imports of metal attained new heights in 1942—a total of 38,911 flasks. It is expected that imports of metal will gain notably in 1943 because of anticipated receipts of constant amounts from Mexico, of substan-

tially more than double the quantity obtained from Canada in 1942, and of 2,000 flasks from Chile.

As exports of mercury were under strict control, the happy balance between production and consumption in the United States in 1942 would have permitted a stock-pile accumulation of virtually all the metal imported had not a large demand for metal developed in the U. S. S. R. and an urgent order been placed in the United States. The demand was due in large part to occupation of the principal Russian source of mercury, the Donets Basin, by the German Army. From October 1942 through February 1943 exports to the U. S. S. R. were officially reported to have totaled nearly 21,000 flasks.

Salient statistics of the mercury industry in the United States, 1938-42
[Flasks of 76 pounds]

1938	1939	1940	1941	1942
17, 991	18, 633	37, 777	44, 921	50, 846
91	107	159	197	184
\$75.47	\$103. 94	\$176.87	\$185.02	\$196. 35
\$66.92	\$88. 26	\$201.10	\$194.20	\$227. 87
179, 522	265, 944	12, 971	588, 228	2, 957, 264
2, 362	3, 499	171	7, 740	38, 911
54, 161 713 1 19, 600	91, 789 1, 208 1 20, 900	730, 877 9, 617 26, 800	196, 837 2, 590 44, 800	593, 311 7, 807
	17, 991 91 \$75. 47 \$66. 92 179, 522 2, 362 54, 161	17, 991 18, 633 107 \$75. 47 \$103. 94 \$88. 26 179, 522 265, 944 2, 362 3, 499 54, 161 91, 789	17, 991 18, 633 37, 777 159 107 159 \$75. 47 \$103. 94 \$176. 87 \$201. 10 179, 522 265, 944 12, 971 2, 362 3, 499 171 54, 161 91, 789 730, 877	17, 991 18, 633 37, 777 44, 921 197 159 197 197 159 197 197 159 197 197 159 197 197 159 197 197 197 197 197 197 197 197 197 19

<sup>&</sup>lt;sup>1</sup> Apparent consumption.

Office of Price Administration.—Price-ceiling action taken by the Office of Price Administration in February 1942 was described in the

Mercury chapter for 1941.

Metals Reserve Co.—In April, when permitted consumption lagged behind supplies available from domestic mines, the Metals Reserve Co. arranged to purchase surplus spot mercury from current domestic production at \$192 a flask, f. o. b., New York. The program was enlarged in July to make it possible to dispose of metal at purchase depots established at many points throughout the country, and at that time it was extended conditionally through December 31, 1943. On March 30, 1943, the program was extended to December 31, 1944, with certain modifications regarding termination of purchases before that date. In projecting purchase agreements into the future, the Metals Reserve Co. recognized the premise that a sustained price, if at satisfactory levels, will insure greater production than will a rising price that may reverse itself at any moment.

Consumption restrictions.—Conservation Order M-78, issued January 23, 1942, restricted the use of mercury for certain purposes and discontinued its use for certain others; it was described in the Mercury chapter for 1941. In August 1942 the order was amended to add fireworks and preparations for film developing to the list of discontinued uses. The use of mercury for cosmetics or any preparation designed for bleaching the skin or removing freckles was cut to 30 percent.

for bleaching the skin or removing freckles was cut to 30 percent.

Bureau of Mines and Geological Survey activities.—In continuing its search for strategic minerals, the Bureau of Mines investigated deposits of mercury in Idaho, Oregon, Nevada, California, and Alaska during the year.

 $\cdot$  715 MERCURY

An extensive area of mercury mineralization near the head of Cinnabar Creek in Valley County, Idaho, has been known since 1917. During 1941 and 1942 the Bureau of Mines completed 9,118 feet of diamond drilling on the Hermes, Annie Sell, and Pretty Maid claims, which resulted in the discovery of a large tonnage of commercial ore. It is estimated with reasonable assurance that underground operations upon a commercial basis may be continued for 3 to 5 years at a rate of about 300 flasks of mercury per month.

Early in 1942 the Bureau of Mines and the Geological Survey made preliminary examination of the Black Butte mine, south Lane County, Oreg. As a result of systematic sampling, which consisted of diamond drilling and extensive channel sampling on the 400-, 900-, and 1,100foot mine levels, a large tonnage of low-grade ore was indicated.

Under a project called the Silver Spots Program, preliminary sampling was done on the following properties in Nevada: Reward Quicksilver mine, Mineral County; F and L Quicksilver mine, Esmeralda County; Mercury Mining Co., Nye County; Washington Hill property, Storey County; Thompson Quicksilver property, Nye County; B and B mine, Esmeralda County; Nevada Cinnabar mine, Nye County; Last Chance mine, Bottle Creek district; Rand mine, Ivanhoe district; Buckskin Peak, National district; and the Pershing Quicksilver mine, northeast of Lovelock. In Oregon the Bureau of Mines is conducting further exploration by churn drilling on the Bretz property in Malheur County.

The Guadalupe mine, 10 miles south of San Jose, Calif., is in one of the most productive mercury areas of the State. The Bureau of Mines has continued exploration in this area. The work has comprised trenching and test pitting of old dumps, as well as trenching and drilling of promising areas in search of new ore bodies; a sub-

stantial tonnage of low-grade ore is indicated.

Investigation and exploration continue on the mercury deposits in the Sleitmut area along the Kuskokwim River, Alaska. Devil mine was explored during the summer and autumn of 1942, and a large tonnage of high-grade ore has been indicated. Other proved claims in the area include the Willis and Barometer and a number of small prospects where a potential reserve of 5- to 15-pound ore is available.

During 1942 the Geological Survey published reports on the mercury deposits of the Stayton 1 and Parkfield 2 districts, Calif.; Pike County, Ark.3; Wildhorse district, Nev.4; and Opalite district, Oreg. and Nev.5 The Survey also issued general papers on the status of the industry6 and concepts on the geology of mercury deposits in the United States.7

In California, field work was completed in the Guerneville district, Sonoma County, and the New Idria district, San Benito County.

<sup>1</sup> Bailey, E. H., and Myers, W. B., Quicksilver and Antimony Deposits of the Stayton District, Calif.: Geol. Survey Bull, 931–Q, 1942, pp. 405–434.

1 Bailey, E. H., Quicksilver Deposits of the Parkfield District, Monterey and Kings Counties, Calif.: Geol. Survey Bull. 936–F, 1942, pp. 143–169.

3 Gallaeher. D., Quicksilver Deposits near the Little Missouri River, Pike County, Λrk.: Geol. Survey Bull. 936–H, 1942, pp. 189–219.

4 Dane, C. H., and Ross, C. P., The Wildhorse Quicksilver District, Lander County, Nev.: Geol. Survey Bull. 931–K, 1942, pp. 259–278.

4 Yates, R. G., Quicksilver Deposits of the Opalite District, Malheur County, Oreg., and Humboldt County, Nev.: Geol. Survey Bull. 931–N, 1942, pp. 319–348.

6 Ross, C. P., Mercury Mining Today in the United States: Eng. and Min. Jour., vol. 143, No. 9, September 1942, pp. 55–58.

7 Ross, C. P., Some Concepts on the Geology of Quicksilver Deposits in the United States: Econ. Geol., September-October 1942, pp. 439–465.

A drilling project by the Bureau of Mines at New Idria, begun late in 1941, was completed. Geologic facts disclosed by drilling and by the Survey's detailed geologic mapping and interpretations are credited by the management as having led to the discovery of important new ore bodies. At the end of the year field work was in progress in the New Almaden district, Santa Clara County; Wilbur Springs district, Lake and Yolo Counties; Sulphur Bank district, Lake County; and the northwest and southeast parts of the Mayacmas district, Lake, Napa, and Sonoma Counties. A cooperative drilling and dump-sampling program was begun at the Guadalupe mine, New Almaden district, by the Geological Survey and Bureau of In Texas an exhaustive geologic study of all the mines in the Terlingua district was begun early in 1942 and was still in progress at the year end. In Oregon field work was completed on the Bonanza-Nonpareil and Horse Heaven districts, in Douglas and Jefferson Counties, respectively. Work was also in progress in the Meadows, Ochoco, and Blackbutte districts in Jackson, Crook, and Lane Counties. In Nevada, detailed geologic studies of the Pilot Mountains, Ivanhoe, and Relief (Antelope Springs) districts in Mineral, Elko, and Pershing Counties were completed. In addition to these larger districts, the Bureau of Mines and Geological Survey concluded a comprehensive sampling and mapping program that included nearly all the districts and isolated mines in the State and yielded concrete data on the reserves of commercial and marginal ores in Supplementary reports were prepared on the only mercuryproducing district in Washington and on the several mines in Arkansas. A detailed geologic study was made of the highly productive Hermes mine, Valley County, Idaho.

Preliminary investigations in Alaska were conducted at Decoursey Mountain, about 50 miles northwest of the Sleitmut area. In the Aleknagik area, Tikchik district, Southwestern Alaska, one promising prospect was investigated, and detailed but unsuccessful search was made for the bedrock sources of placer cinnabar in the Seventymile area in the Yukon region. In the Sleitmut area, Georgetown district, Southwestern Alaska, the Geological Survey continued investigations on five properties that were trenched and sampled by the Bureau of Mines. This work resulted in much more adequate deter-

mination of the surface outlines of several large ore bodies.

In Latin America detailed studies of the three most important mercury districts in Mexico—Nuevo Mercurio, Sain Alto, and Huahuaxtla—were made by the Geological Survey in the course of cooperative work with the Department of State. The work has been followed by significant increases in production. Study of an important prospect in Colombia was undertaken in cooperation with the Board of Economic Warfare.

Tests for mercury.—Since the outbreak of the present World War there have been many requests for information regarding specifications for mercury, tests to ascertain its purity, and other data along these lines. An article by Wichers <sup>8</sup> should be of interest in this connection.

<sup>&</sup>lt;sup>8</sup> Wichers, Edw., Pure Mercury: Chem. and Eng. News, vol. 20, No. 17, September 10, 1942, pp. 1111-1112.

のである。 大きなないとのでは、 「これでは、 「これでは、 「これでは、 「これでは、 「これでいっとのかっとう」。

#### Wichers states

Virgin mercury, that is, mercury as produced at the mines, usually has a bright, mirrorlike surface and is clean except for traces of scum or perhaps particles of rust or other foreign matter from dirty containers. If such mercury is filtered through a pinhole in a paper cone, a glass filtering crucible, or several thicknesses of finely woven cloth into a clean, dry glass vessel and thereupon retains a bright and clean appearance, one can be sure that it does not contain so much as one part per million of any base metal. Metals more noble than mercury, that is, silver, gold, and platinum group elements, are not disclosed, but virgin mercury is not likely to contain them in amounts as great as a few parts in a million. Reclaimed mercury is generally as clean as the virgin metal, but may contain more of the noble metals because it is not always subjected to distillation in the reclaiming

The statement that mercury which looks clean and does not show the behavior known as tailing is at least 99.9999 percent pure with respect to base metals may be challenged by many readers. It is indeed hard to believe that any commercial substance possesses such an exceptional degree of purity. But it can be demonstrated quite readily. To do so, drop about 0.5 mg. of tin foil into 100 grams of clean mercury in a small beaker or Erlenmeyer flask. Swirl the mercury around for a minute or so and observe the skin or crust that forms almost im-I think the observer will agree that the visible effect can be safely mediately. extrapolated to less than one part of tin in a million of mercury. Similar trials can be made with other base metals. The visible effects will not be exactly alike or appear equally rapidly, but they will be equally unmistakable.

#### PRICES

Monthly prices for mercury rose steadily throughout 1941 and into January 1942. Ceiling prices were established by the Office of Price Administration in February 1942; the details of the order (Price Schedule 93) were outlined in the Mercury chapter for 1941. Broadly, the prices ranged from \$191 to \$193 a flask, depending on the point of shipment. All other kinds and grades were to be sold at their normal differentials from the maximum prices established. Amendment 1 to Price Schedule 93 provided that, effective February 10 and until March 2, 1942, the schedule was not applicable to dealers who had mercury on hand or in transit on February 4 to meet contracts made before February 4. Press Release PM 2731, issued March 19, 1942, explained that the 2-percent premium allowed to dealers under the regulation could be split with another dealer or a broker but not with a producer if this would result in the producer obtaining more than the applicable maximum price. Amendment 1 to Revised Price Schedule 93 defined "mercury" as prime virgin mercury, redistilled mercury, reclaimed mercury, and all other kinds and grades of mer-The amended schedule provided that, effective July 7, all kinds and grades of mercury sold in containers of 25 pounds or less should be sold and bought for not more than the normal differentials prevailing between October 1 and 15, 1941.

Under maximum price limitations the monthly quoted prices fell from \$202.52 in January to \$194.28 in June, remained at \$194.43 for 3 months, and then advanced to \$196 in November and December.

There is no evidence that any change has occurred in the average price for Spanish and Italian metal in what, for convenience, may be called the international market. As Germany was probably the principal consumer of mercury from these sources in 1942 and inasmuch as German methods of payment probably do not lend themselves to the restrictions of fixed prices, there is little question that the price indicated for Spanish and Italian metal was purely nominal.

The Control maximum prices for mercury in London were £48 15s. a bottle for over 1 bottle and less than 11 bottles and £48 for larger quantities, ex-sellers' premises in both cases. The prices were raised to £69 15s. and £69 in August, and they remained at these levels beyond the end of the year. Higher prices prevailed for lots under 1 bottle and for redistilled grades. There was speculation as to whether or not the advance in prices coincided with British purchased of Spanish metal.

Average monthly prices per flask (76 pounds) of mercury at New York and London and excess of London price over New York price, 1940-42

		1940			1941		1942		
Month	New York 1	Lon- don 2	Excess of London over New York	New York 1	Lon- don 2	Excess of London over New York	New	Lon- don 2	Excess of London over New York
January	\$156.96	\$169.50	\$12.54	\$165.85	\$193.64	\$27, 79	\$202. 52	\$194.69	3 \$7, 83
February	178.00	207.00	29.00	170.18	193. 43	23. 25	197. 27	194. 69	3 2. 58
March	180. 92	207.00	26.08	177.69	193, 53	15.84	197.05	194. 68	3 2. 37
April	173. 54	181. 32	7.78	180.08	193, 19	13.11	197.10	194. 69	3 2. 41
May	181. 54	168. 34	3 13, 20	180.00	194. 50	14.50	197. 30	194.69	3 2. 61
June	197.36	189.44	3 7, 92	183. 92	194. 52	10.60	194. 28	194. 69	. 41
July	194.42	207. 36	12.94	188. 58	194, 56	5. 98	194. 43	194.69	:26
August	184.11	216.84	32.73	192.00	194. 53	2. 53	194. 43	257. 56	63. 13
September	173. 33	219.86	46. 53	192.44	194.58	2.14	194. 43	278. 52	84.09
October	168.85	219.78	50.93	193.62	194. 59	. 97	195. 35	278. 52	83, 17
November	168. 39	219.94	51.55	196. 27	194.65	3 1.62	196.00	278. 52	82. 52
December	164. 96	206. 79	41.83	199.65	194. 69	3 4. 96	196.00	278. 52	82. 52
Average	176. 87	201.10	24. 23	185. 02	194. 20	9. 18	196. 35	227. 87	31. 52

New York excess.

# CONSUMPTION

Requirements for mercury gained in 1942 despite the restrictions placed on certain uses by the War Production Board, and a new high record rate of consumption was attained. Consumption was relatively stable in the first 3 quarters of the year, amounting to 10,300, 11,500, and 11,000 flasks. A 55-percent rise took place in the fourth quarter owing to some special orders for military purposes. Consumption in the 5-year period 1938-42 is shown in the following table, figures for 1938 and 1939 having been computed by the conventional method of adding production to imports and deducting exports, because of the absence of more precise information.

Data showing consumption of mercury by uses are shown in the second table following.

Supply of mercury in the United States, 1938-42, in flasks of 76 pounds

Year	Production	Imports for consumption	Exports	Consumption
1938.	17, 991	2, 362	713	1 19, 600
1939.	18, 633	3, 499	1, 208	1 20, 900
1940.	37, 777	171	9, 617	26, 800
1941.	44, 921	7, 740	2, 590	44, 800
1942.	50, 846	38, 911	7, 807	49, 700

<sup>1</sup> Apparent consumption.

<sup>&</sup>lt;sup>1</sup> Engineering and Mining Journal, New York.

<sup>2</sup> Mining Journal (London) prices in terms of American money through March 1940. Thereafter prices in terms of pounds sterling are converted to American money by using average rates of exchange recorded by Federal Reserve Board. Official prices, established early in May 1941, were £47 15s. to £48 15s. per flask until August 1942, when they were raised to £68 10s. to £69 15s.

Mercury consumed in the United States in 1942, in flasks of 76 pounds

Use	Flasks 1	Use	Flasks 1
Pharmaceuticals Dental preparations Fulminate: Munitions Blasting caps Munitions other than fulminate Agriculture Antifouling paint	8, 088 1, 198 } 4, 146 3, 684 1, 533 1, 220	Electrical apparatus Industrial and control instruments Amalgamation General laboratory use Vermilion Felt manufacture Redistilled Other	4,550 23,529 180 294 215 20 26,175 39,103
As a catalyst or in the electrolytic preparation of— Chlorine Caustic soda Acetic acid Other	} 549 1,410 1,843		1 49, 700

1 The items are on a partial-coverage basis and do not add to the total, which has been increased to cover

approximate total consumption.

About half of the quantity shown under "Redistilled" was for use in industrial and control instruments.

Of this total, 1,028 flasks were for a new chlorine-plant installation and to replace mercury-boiler leakages. It is deemed inadvisable at this time (May 1943) to divulge details covering 4,700 flasks.

Inasmuch as figures for 1941 were not obtained for the entire year upon the same basis, possibly the best means of comparing 1941 and 1942 data is to examine the total for 1942 in comparison with double the quantities reported for the latter half of 1941. Upon this basis the 1942 totals compare with 1941 as follows: Pharmaceuticals +51 percent, dental -2, fulminate +29, agriculture -61, vermilion -79, antifouling paint -10, felt manufacture -98, chlorine and caustic soda +77, acetic acid -15, other catalytic use -23, and amalgamation -44 percent. Production of redistilled mercury from virgin metal used 43 percent more metal in 1942 than twice the amount used in the latter half of 1941, and "other" uses were up well over 600 Supplemental canvasses in 1941 and 1942 show that 50 percent or more of the metal redistilled is used to make industrial and control instruments, 16 percent for electrical apparatus, and 14 percent for dental purposes. A break-down of the quantities shown as "redistilled" in the table, therefore, would add substantially to the amounts used for these purposes. "Other" in 1942 includes mercury amounting to 4,700 flasks, the uses of which it is inexpedient to reveal at this time. Also reported under the "Other" class in 1942 are 1,028 flasks used in a new electrolytic chlorine-plant installation and in replacing metal leakages in mercury power boilers.

#### STOCKS

Inventories of mercury in the hands of consumers and dealers amounted to about 10,700 flasks at the end of 1942 compared with 12,400 at the end of 1941 and 14,100 at the end of 1940. On January 3, 1942, Metals Reserve Co. stocks totaled 5,408 flasks, and the Procurement Division of the Treasury Department held 2,050 flasks. On December 31, 1942, the Metals Reserve Co. had 17,416 flasks and the Procurement Division 9,994. Companies that use redistilled metal only held 2,400 flasks at the end of 1942 compared with 1,600 at the end of 1941. Stocks held by companies that report mine production monthly to the Bureau of Mines—about 95 percent of the total—were 1,377 flasks on December 31, 1942, compared with 439 flasks at the end of 1941.

## REVIEW BY STATES

Under the stimulus of the highest annual price ever obtained and the assurance of a stable price, domestic producers gave a very good account of themselves in 1942; output was the highest since 1882. It is significant that the satisfactory quantity recovered was, for the most part, from mines whose names have been famous in mercury history for many years. The most important newcomer in 1942 was the Hermes mine (Idaho) of Bonanza Mines, Inc., just as the chief one in the recent past was the Bonanza mine (Oregon), operated by the same company.

The number of producing mines dropped from 197 in 1941 to 184 The number in both years is very impressive in view of the fact that only about 20 mines 9 were active during the boom

mercury period in the seventies.

Despite their excellent production record, producers were hampered by the same problems that beset other mining industries in 1942. particularly labor difficulties. Not only was the supply of labor insufficient, but available new workers were claimed to be very The inadequate labor supply impeded development work, and operators claimed this condition would doubtless have an early adverse effect on the rate of output.

Mercury produced in the United States, 1939-42, by States

Year and State	Pro- ducing mines	Flasks of 76 pounds	Value 1	Year and State	Pro- ducing mines	Flasks of 76 pounds	Value 1
1939: Arkansas. California. Nevada. Oregon. Arizona, Idaho, and Texas.	5 59 25 14	364 11, 127 828 4, 592 1, 722	\$37, 834 1, 156, 540 86, 062 477, 293 178, 985	1941: Arizona Arkansas California Nevada Oregon Utah	5 19 87 54 21 1	4, 238	\$161, 522 372, 260 4, 757, 604 784, 115 1, 671, 101 3, 515
<b>1940:</b>	107	18, 633	1, 936, 714	Alaska, Idaho, Texas, and Washington	10 197	3, 033 44, 921	561, 166 8, 311, 283
Alaska Arizona Arkansas California Nevada Oregon Utah Idaho, Texas, and	1 6 10 70 42 23 1	5, 924	28, 653 130, 884 204, 992 3, 294, 911 1, 047, 778 1, 599, 436 9, 374	1942: Arizona Arkansas California Nevada Oregon Alaska, Idaho, Texas,	7 16 85 40 23	701 2, 392 29, 906 5, 201 6, 935	137, 641 469, 669 5, 872, 043 1, 021, 217 1, 361, 687
Washington	159	2,067 37,777	365, 590 6, 681, 618	Utah, and Washington	13	5, 711 50, 846	1, 121, 35 9, 983, 61

<sup>1</sup> Value calculated at average price at New York.

The principal producing mines in 1942 were as follows:

Arizona—Maricopa County, Pine Mountain mine.
Arkansas—Clark County, Humphreys mine; Pike County, Arkansas Quicksilver group (Parker Hill and Gap Ridge).
California—Contra Costa County, Mount Diablo mine; Lake County, Great Western, Sulphur Bank, Abbott and Mirabel mines; Napa County, Knoxville and Oat Hill mines; San Benito County, Lea-Grant and New Idria mines; San Luis Obispo County, Oceanic and Klau mines; Santa Barbara County, Santa Ynez (Falcon) and Red Canyon (Red Rock) mines; Santa Clara County, New Almedon mine and Almedon dumps; Sonoma County, Socrates Great Eastern. Almaden mine and Almaden dumps; Sonoma County, Socrates, Great Eastern, and Mount Jackson mines; Yolo County, Reed mine.

<sup>&</sup>lt;sup>6</sup> Ross, C. P., Mercury Mining Today in the United States: Eng. and Min. Jour., vol. 143, No. 9, September 1942, p. 55.

Idaho—Valley County, Hermes mine; Washington County, Idaho Almaden mine.

Nevada—Humboldt County, Cordero and White Peak mines; Pershing County, Red Bird and Pershing mines.

Oregon—Douglas County, Bonanza mine; Jefferson County, Horse Heaven mine; Malheur County, Bretz mine.

Texas—Brewster County, Chisos and Big Bend and Texas Almaden mines; Presidio County, Fresno mine.

These 34 mines produced 89 percent of the United States total. The 33 most important mines produced 85 percent of the total in 1941, 29 produced 86 percent in 1940, and 16 produced 88 percent in 1939.

Several of the mines that were included in the group of 33 principal mines in 1941 were closed or virtually closed at the end of 1942. These were the Caddo, Contact, Idaho-Almaden, McAdoo group, Mount Tobin, Opalite, and Chisos. The Caddo and Opalite resumed production early in 1943. The Chisos has gone into bankruptcy, and no plans to reopen this famous old mine have been announced.

Before World War I the tenor of mercury ores treated in the United States averaged more than 10 pounds per ton or over 0.50 percent. The inclusion in the 1918 figures of a large quantity of low-grade material that was rejected before concentration at Sulphur Bank was partly responsible for the reduction in average grade to 6 pounds or 0.30 percent in 1918. In consideration of the sharply increased price paid for mercury in World War II, it is somewhat remarkable that the grade of ore treated has not fallen more rapidly. Dump material has been excluded insofar as possible from the grades shown for recent years, but separation of newly mined ore and dump material for many large mines (the New Idria is one of them) is not possible. The average grade indicated for 1942 was 0.25 percent (5-pound ore), compared with 0.26 percent (5.2-pound ore) in 1941, 0.31 percent (6.2-pound ore) in 1940, and 0.37 percent (7.4-pound ore) in 1939.

Alaska.—Output from Alaska came from Decoursey Mountain and Sleitmut areas, where geologic studies and drilling campaigns were carried on by the Geological Survey and the Bureau of Mines.

Arizona.—Production in Arizona declined from 873 flasks in 1941 to 701 flasks in 1942. The Pine Mountain, Ord, and Rattlesnake mines were the principal producing properties, and four others contributed to the total. Production was confined to Gila and Maricopa Counties.

Arkansas.—Fewer mines contributed to production in Arkansas in 1942 than in 1941, but a new record (by 19 percent) was established nonetheless. By far the largest producer was the Humphreys Gold Corporation property in Clark County. The Arkansas Quicksilver Mines, Inc., stood out in Pike County, and other large contributors in the State included the Caddo, Big Six, Superior, and U. S. Mercury.

The Humphreys Gold Corporation began development work in the summer of 1941 and in 1942 treated 18,758 tons of ore and recovered 1,176 flasks of mercury. In the final quarter of 1942 the production

rate approximated 145 flasks a month.

California.—California increased its predominant position in mercury production in 1942, with an output of 29,906 flasks or 59 percent of the total, compared with 25,714 flasks or 57 percent of the total in 1941. All the California mines that ranked among the principal producers in 1941, except the Contact, were again prominent

in 1942, and the Abbott, Lea-Grant, Red Canyon (Red Rock), and Socrates joined the leaders. The Socrates mine was operated by the company that ran the Contact in 1941. An outstanding reason for the favorable California showing was the performance of the New Idria mine, whose output was more than double that of the next most important producer in the country in 1942 and was substantially more than equal to the combined total for the next three most important producers. The Sulphur Bank, New Idria, Klau, Mount Jackson, and Reed mines each produced nearly or more than 2,000

Sixteen counties in California supplied some production in 1942, as follows: Colusa, Contra Costa, Fresno, Inyo, Kings, Lake, Napa, San Benito, San Luis Obispo, Santa Barbara, Santa Clara, Siskiyou,

Sonoma, Stanislaus, Trinity, and Yolo.

At the Abbott mine, Lake County, the shaft was deepened 100 feet. The Mirabel mine, also in Lake County, produced 720 flasks of mercury from 7,317 tons of ore. Some production was reported for the Helen mine, which has since been taken over by the Anglo-American Mining Corporation, etd. Altogether, 10 mines in Lake County reported mercury projection in 1942.

Production of the win Peaks Mining Co. was shifted from the Twin Peaks in 1941 to the Corpora mine, Napa County, in 1942. A

total of 4,915 tons of ore from the Corona mine was treated in the new plant at the adjacent Twin Peaks mine, and 203 flasks of mercury were produced. Zack Anderson (operating the Oat Hill Extension mine in the same county) reported the construction of a 40-ton mill which in May 1943 he anticipated would soon be in operation. Nine

other properties in Napa County reported some production.

At the Lea-Grant mine, Panoche district, San Benito County, about 10,000 tons of ore were treated to recover 291 flasks of mercury. This mercury property is one of those in which the Marsman Co. of California became interested before the end of the year, the others being the Altoona in Trinity County, Calif., and the Reward in Mineral County, Nev. Greatly expanded operations were carried on by the New Idria Quicksilver Mining Co. at the New Idria mine in 1942, and production was materially higher. This mine sharply increased its lead over all others in the country, and further gains are anticipated in 1943. At the Panoche mine 11,303 tons of ore were treated and 197 flasks of mercury produced in a 4- by 64-foot rotary Fourteen other mines in the county were productive.

A new bank of steel condenser pipes was installed at the Oceanic mine, San Luis Obispo County. Ore from the Echo Butte (Little Bonanza group) was furnaced at the Oceanic plant. The shaft at the Klau mine in being deepened by 100 feet from the present 450-foot level, and a new level will be developed. At the Polar Star mine 90 tons of ore were treated in a retort and 63 flasks of mercury produced. This mine was under option to Lawrence Requa at the end of the year.

Production came also from 6 other mines in the county.

The Red Canyon Mining Co. was superseded by the Cachuma Mining Co. in operation of the Red Rock mine, Santa Barbara County. Together they treated 10,450 tons of ore, which yielded 613 flasks of mercury. The Santa Ynez mine was again operated by Geo. H. Hall, who made an important output, and one other property in the county made a small contribution to the total.

TO A THE PARTY OF 
The state of the s

Section of the second

In the early part of 1942 Aalders and Prather operated the Amenden dumps, Santa Clara County, which subsequently were operated by Sam Cohen. Cohen left the property before the end of the year owing to "litigation over alleged pollution of creek." The New Almaden mine has been opened to the 800-foot level through the Day tunnel. The Santa Rita shaft was reopened, and a 150-ton pocket was built on the 800-foot level. An important production, roughly three-fourths of which came from dumps, was made by this mine in 1942. The Guadalupe and seven other mines in Santa Clara County were also productive.

The Mount Jackson was the principal producing mine in Sonoma County in 1942. At the Great Eastern mine 605 flasks of mercury were recovered from 21,966 tons of ore. Sinking the shaft to the 500-foot level and crosscutting 320 feet northwest were hoped to develop considerable additional ore. The Culver-Baer produced 112 flasks from 263 tons of ore. Development work at the Socrates mine is reported to have promised additional ore reserves. The Contact mine was flooded in January 1942; its future is undetermined. Seven

other mines in the county produced in 1942.

The Reed mine in Yolo County was one of the outstanding pro-

ducers in the country as well as in the State.

Idaho.—The promise of another important producer in Idaho was brought to fruition in February 1942 when the Hermes mine became a substantial contributor. Monthly successive gains were made at this mine throughout the year, and for December 1942 it ranked as the second-largest producer in the country. This property is more than offsetting the loss of production from the Idaho-Almaden mine, which closed in December owing (according to the operator) to exhaustion of commercial ore.

Nevada.—Production in Nevada gained 23 percent, rising from 4,238 flasks in 1941 to 5,201 flasks in 1942, although it came from only 40 mines compared with 54. The noteworthy increase was due largely to expansion in production at the Cordero mine, principal producer in the State by a substantial margin in 1942 and one of the outstanding producing properties in the country. Productive operations were carried on in Elko, Esmeralda, Humboldt, Mineral, Nye, Pershing,

and Storey Counties.

The Mount Tobin mine, Pershing County, an important producer in 1941, made an output during January and February only in 1942. The principal producing mine in the county was the Pershing, which had been inactive since 1930. A total of 18,041 tons of ore was treated and 855 flasks of mercury produced. The next largest was the Red Bird, where a Gould furnace was completed early in 1943. Williamson & Garteiz produced 127 flasks at the Roman mine, a newly developed property. Eight other mines produced in 1942.

Operations at the Corder's mine, Humboldt County, were described by Williston. Of Greenan produced 343 flasks of mercury from 2,500 tons of ore at the White Péak mine and 4 flasks from 30 tons at the Red Ore. The McAdoo properties contributed little to the State total after January 1942, following the substantial amounts produced in 1941. Altogether nine mines in Humboldt County reported

production.

<sup>&</sup>lt;sup>10</sup> Williston, S. H., Mining Quicksilver in Nevada: Min. Cong. Jour., vol. 28, No. 11, November 1942, pp. 24–28.

Seven mines in Mineral County reported some output in 1942; the chief was the Reward mine.

Four mines in Nye County were productive in 1942. The Horse Canyon mine produced 6 flasks from 58 tons of ore and was abandoned.

Oregon.—Oregon experienced a sharp set-back in production in 1942, although maintaining its position as second-largest mercuryproducing State. The 1942 total was 6,935 flasks compared with 9,032 in 1941, a drop of 23 percent, and Oregon's share of the United States total was 14 compared with 20 percent in 1941. An outstanding reason for the drop was the decline in output from the Bonanza, which, however, maintained its noteworthy lead in Oregon and held second place among the mines of the country. Other important producers were the Horse Heaven in Jefferson County and the Bretz in Malheur County. Clackamas, Crook, Harney, Jackson, Lake, and Lane Counties also reported some production.

Texas.—Production in Texas rose in 1942, but the year witnessed the passing into bankruptcy of the famous old Chisos mine, which was idle during the last several months. This mine had been in virtually continuous operation for 40 years. It is in the Terlingua region, which according to Ross 11 has had a total production exceeding 150,000 flasks and perhaps comprising nearly 200,000 flasks. The Chisos has contributed by far the greatest part of this total. Its output from 1902 or 1903 to the present ranks it historically as the fourth-largest producing mercury mine in the United States.

# FOREIGN TRADE 12

Under the stimulus of Metals Reserve Co. purchase agreements, imports of mercury in 1942 were the highest on record by a wide margin. Imports for consumption amounted to 38,911 flasks, considerably more than had been received in the 5-year period, 1937-41. The preponderant part-29,918 flasks-came from Mexico, 7,564 from Canada, and 1,409 from Chile; 20 flasks were credited to Nica-The movement of mercury to the United States from normal sources was cut off in 1940. Mercury began to arrive from other sources in August 1941. In November and December 1941, 6,861 flasks were received out of the total imports for the year of 7,740 There was wide variation in the amounts of mercury received in 1942, by months, from a low of 1,791 flasks in August to a peak of 6,374 flasks in December. There was a difference of only 10 flasks between imports for consumption and general imports in 1942.

In addition to the mercury received from Mexico in the form of metal during 1942, antimony-mercury concentrates imported from that country yielded 1,050 flasks during the year compared with 1,300 each in 1941 and 1940. This latter class of imports is not shown separately in foreign trade statistics.

Ross, Clyde P., The Quicksilver Deposits of the Terlingua Region, Texas: Econ. Geol., vol. 36, No. 2, March-April 1941, pp. 115-142.
 Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

からまかました 日本の事をというというというというと

Mercury imported into the United States, 1938-42, by countries

	19:	1938		1939		1940		1941		1942	
Country	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value	
Canada							59, 633	\$130, 468	574, 888 107, 091	\$1, 365, 690 266, 920	
Germany Hong Kong					3	\$6			.1	2	
Italy Mexico	84, 454	\$50, 434	25, 528 42, 745	\$29, 818 61, 313		316 13, 681	520, 692	1, 171, 752	2, 273, 739 1, 545	5, 088, 709 3, 395	
Nicaragua Spain	95, 068	82, 176	197, 671	245, 613	3, 042	3, 958	7, 903	6, 373			
	179, 522	132, 610	265, 944	336, 744	12, 971	17, 961	588, 228	1. 308, 593	2, 957, 264	6, 724, 716	

Imports of mercury compounds were virtually nonexistent during 1941 and 1942, as is shown by the table that follows. Early in 1940 the increased receipts of mercury compounds from Italy had been a minor threat, at least, to the domestic industry; all imports from Italy, both as metal and as compounds, ceased officially in 1940. A large shipment of metal and compounds in 1941, however, credited to Portugal and subsequently exported, has presented some food for speculation.

Mercury compounds imported for consumption in the United States, 1941-42

			1	1942		
Compound		Pounds	Value	Pounds	Value	
Chloride (mercurous) (calomel) Mercury preparations (not specifically provided for) Vermilion reds (containing quicksilver)		25 24 25	\$83 140 9	1 12 25	\$4 132 10	
			232		146	

Exports of mercury, under Government control since July 1940, dropped from 9,617 flasks in 1940 to 2,590 in 1941 and to only 249 in the first 9 months of 1942. The cutting off of most of the domestic mercury supplies of the U. S. S. R. by the German advance into the Donets area brought large orders from the U. S. S. R. for United States metal. In the final quarter of 1942, 7,461 flasks were recorded as having left the United States for the U. S. S. R. This record, however, lagged behind the actual movement of metal because a much greater quantity is known to have gone. The statistical lag was picked up in records for the early months of 1943. In the 5-month period October 1942 to February 1943, inclusive, mercury exports to the U. S. S. R. aggregated nearly 21,000 flasks. Total exports of mercury in 1942 aggregated 7,807 flasks. No country other than Russia received as much as 100 flasks of mercury from the United States in the year. Brazil received the second-largest amount-64 flasks-followed by Canada with 40, Venezuela with 32, Trinidad and Tobago with 30, and 4 dozen others with lesser amounts ranging down to 1 pound.

## Mercury exported from the United States, 1938-42

Year	Pounds	Value	Year	Pounds	Value
1938	54, 161	\$50, 184	1941	196, 837 593, 311	\$470, 903
1939 1940	91, 789 730, 877	137, 427 1, 743, 149	1942	593, 311	1, 519, 227

The Commerce Department began to report exports of mercury salts separately in July 1941. For July 1 to August 31, 1941, totals only were given for mercury salts and compounds; they amounted to 3,213 pounds. No annual comparisons are available for the 1942 totals shown in the following table, but data for the last 4 months of 1941 are given in a parallel column.

Mercury salts exported from the United States in 1941 (September-December) and 1942, in pounds 1

	1941 (Sept Dec.)	1942		1941 (Sept Dec.)	1942
Mercurous chloride (calomel) Mercuric chloride (corrosive sub- limate) Mercuric fulminate Mercuric nitrate	6, 976 9, 496 6, 020 222	22, 844 7, 261 39, 595 477	Mercuric oxide (red and yellow) Mercuric sulfate Mercuric sulfide Other compounds	4, 261 62 5, 170	9,495 15 6 8,518

<sup>1</sup> See preceding paragraph.

## WORLD PRODUCTION

Reliable data are not available on production in Spain and Italy, which dominate the world mercury industry in normal times. Increased rates of operations in Western Hemisphere countries, however, have been such that new world-record tonnages probably were established in 1941 and 1942, even if these two principal countries were operating considerably below capacity. What information has come out of Europe, however, has pointed to heavy mercury operations in both Spain and Italy. The recent gains in Western Hemisphere countries place the United States, Mexico, and Canada among the five most important producing nations and could even have pushed the United States temporarily into second place. The latter is considered a possibility but not a likelihood.

というではたまとれている

# World production of mercury, 1938-42, by countries

#### [Compiled by B. B. Waldbauer]

[1 metric ton=29.008 flasks of 76 pounds]

	19	38	19	39	19	<b>)4</b> 0	19	41	19	42
Country	Flasks	Metric tons	Flasks	Metric tons	Flasks	Metric tons	Flasks	Metric tons	Flasks	Metric tons
Algeria Australia: Queens- land Bolivia (exports) Canada Chile China Chosen Czechoslovakia Germany³ Austria Italy Japan Mexico New Zealand Peru Rumania Southern Rhodesia Spain Tunisia Turkey Union of South Africa U, S, S, R	191 10 44 2 655 (4) 2, 900 1, 750 (6), 748 66, 748 66, 748 67,	1. 5 2 2. 2 (4) 100. 0 60. 2 (4) 2, 301. 0 20. 4 293. 7 . 3	3 9 6 (1) 2 13 (4) 5 2.669 (1) 7, 376 (1) 7, 376 (1) 2 53, 441 (1) 359	(1) (4) (5) 92. 0 (1) (2) (2) (3) (2) (3) (4) (5) (6) (7) (8) (9) (1) (1) (1) (1) (2) (1) (2) (3) (4) (4) (4) (5) (7) (7) (8) (9) (9) (1) (1) (9) (1) (1) (1) (1) (1) (1) (1) (2) (3) (4) (4) (5) (6) (7) (7) (7) (8) (8) (9) (9) (9) (9) (9) (9) (9) (9	2,024 (1) 26,260 (1) 52,582 (1) (1) (1) (1) 11,653	2 215. 8 (1) 5 89. 0 (1) (1) (1) (1) (1)	1, 305 36,000 (1) (1) (1) (1) (1) (1) (23, 137 73  (1) (3 85, 523 (1)	\$ 206. 8 (1) (1) (1) (1) (1) 797. 6 2. 5 (1) (1) \$ 2,948.3 (1) 8. 2	(¹) (1) (1) (1) (1) (1) (1) (1) (1) (1) (1	60.0 (1) (1) (1) (1) (1) (1) (1)
United States Total 3	17, 991	620. 2 5, 167. 5	18, 633	642.3 5, 516.7	(1)	(1)	(1)	(1)	(1)	(1)

<sup>1</sup> Data not yet available.

<sup>2</sup> Exports.

Algeria.—The invasion of North Africa in 1942 returned the resources of most of that area to the United Nations. The Ras-el-ma mine is in the Department of Constantine near the main road from Philippeville to Constantine, in the area where fighting has been in A report from a source believed to be reliable places the output of this mine as 94 flasks in 1939 and 743 flasks in 1940. ore is said to be of poor quality, containing less than 0.5 percent mercury, and production has been possible only in periods of high prices. In 1940 it was reported that the French hoped to obtain a large part of their annual normal consumption of 130 tons of metal from this mine.

Canada.—Production of mercury in Canada has risen precipitously since World War II began. It totaled 6 flasks in 1939, 2,024 in 1940, 7,057 in 1941, and 13,470 in 1942, and further increases are antici-All known occurrences of mercury in Canada are in British The chapters on Mercury in the two previous issues of Columbia. Minerals Yearbook pointed out that the development of the mercury deposit in the Pinchi Lake area, Central British Columbia, by the Consolidated Mining & Smelting Co. of Canada, Ltd., had given the The small British Empire its only important producer of mercury. initial plant installed by the company has been enlarged twice and is reported to be capable of handling 500 tons of ore daily.

<sup>Conjectural.
Estimate included in total.
Slovak Metallurgical Works.</sup> 

<sup>6</sup> Production less than 1 flask or 0.1 metric ton.

January to November, inclusive.
January to November, inclusive.
Production figure published by Metallgesellschaft.

treated is reported to contain 0.5 to 0.75 percent mercury. The geology of the area has been described recently by Armstrong. Considerable stimulus has been given to prospecting for mercury in British Columbia by the development of the Pinchi Lake deposit and by the increase in United Nations requirements for the metal. The Bralorne Mines, Ltd., largest gold producer in British Columbia, became interested in developing a mercury property late in 1942. The claims are on Silver Creek east of Takla Lake, in the Omineca mining district. Several flasks of mercury were produced in 1941 at the Red Eagle group on Yalakom River, 30 miles northwest of Lillooet.

Italy.—About the only report on Italy's mercury production in recent months placed the output of Stabilimento Minerario di Sieli, second-largest producer, at 40,000 flasks in 1941. This output, if matched by those of other producers, would mean a new high record There is every reason to believe that Italy can produce for Italy. over 70,000 flasks of mercury annually if there is need for it. surplus available from Spain and restricted markets for both countries, the need for record rates of output in the two countries could only mean that Axis requirements for mercury had expanded out of proportion to United Nations gains. Large accumulations of stocks would be the alternative, but with manpower at a premium in Italy it would seem strange to expend energy for accumulating excess stocks. According to the October 17, 1942, issue of Mining Journal (London) the State is now directly participating, through the Agrarian Bank and the Iri Holding Trust, respectively, in the two leading mercury companies, Siele and Monte Amiata. Italy is still a member of the Italo-Spanish International Cartel. Virtually the only foreign customer is Germany, which uses I. G. Farbenindustrie as its sole. buying agent.

Mexico.—The expectation of a rapidly increasing production of mercury in Mexico was amply justified, as indicated by the total of 32,443 flasks for 1942 compared with 23,137 flasks for 1941 and 11,653 for 1940. The exports of 30,029 flasks were destined preponderantly to the United States, to which 29,113 flasks were shipped; 763 flasks went to Argentina, 120 to Brazil, 26 to Colombia, 6 to Chile, and 1 to Costa Rica. The War Production Board of the United States anticipated that approximately as much metal would be shipped to the United States in 1943 as in 1942. Mexico is playing a most important role in the solution of United Nations mercury problems.

New Zealand.—Investigations of cinnabar occurrences by the New Zealand Mines Department are reported to have indicated that a small but worth-while tonnage of high-grade ore may be developed. The deposit at Puhipuhi appears to be the only one capable of sustained production.

Peru.—A 20-ton Gould rotary furnace was installed at the Huan-cavelica mine in 1942. Two additional plants, with an expected combined daily capacity of 300 tons, were to be erected, but temporarily at least permit difficulties prevented their leaving the United States after they had been completed.

Spain.—Reports emanating from Germany (Hamburger Fremdenblatt), quoted in Metal Bulletin (London) of October 9, 1942, stated that Spain produced 85,523 flasks of mercury in 1941 and that 40,695

<sup>&</sup>lt;sup>13</sup> Armstrong, J. E., Geology of the Pinchi Lake Mercury Belt, British Columbia: Canadian Min. and Met. Bull. 362, June 1942, pp. 311–323.

MERCURY 729

flasks were sold (of which 706 were for use at home and 39,989 for export); also that stocks at the Almaden mine at the beginning of 1942 totaled 66,000 flasks. If this report is true, production was 18 percent higher in 1941 than in 1927 and therefore was at a new all-time record rate. It is rather difficult to understand, however, why an effort was made to produce a record quantity in view of the fact that the war has caused a shrinkage in Spanish markets. Metal is reliably reported to have moved from Spain to Germany in large quantities in the early part of 1941. It is only logical to assume, however, that with Italy able to supply much more mercury than is ordinarily required in Germany, purchases of Spanish metal in Germany would drop to insignificant proportions. Political considerations, of course, could affect German policy in this connection. In explanation of the high rate of production in Spain, an article in Engineering and Mining Journal of May 1942 says—

\* \* \* By law, in Spain, no workman of regular crew may be laid off without long advance notice. Hence, either production must go on at a minimum rate, or payroll with no output must be maintained. It is for this reason that such a huge inventory has been accumulated \* \* \* \*.

The cartel price had an adverse effect on sales to the United Kingdom. Purchases have been made in the United Kingdom since the war started, however, and in August 1942 the London price was raised from £48 to £69, the latter figure corresponding more closely with


the cartel price.

Union of South Africa.—Output in the Union is increasing steadily according to Preller.<sup>14</sup> In the chapter on Mercury in Minerals Yearbook, 1941, it was pointed out that some anxiety was felt in that country regarding supplies of mercury. Preller states that production at Monarch Kop in 1942 had fallen not far short of requirements in the Union and that an excess over local consumption might result in 1943. The cinnabar at Monarch Kop occurs with lenticles of quartz and crystalline carbonate in chloride-carbonate schists through a thickness of 15 to 20 feet in places. The deposit is reported to show great

promise as far as consistency and extent are concerned.

U. S. S. R.—The principal producing area in the U. S. S. R. has been the Donets Basin. Output from this source has been lost temporarily owing to German occupation of the territory. Production is now coming from other localities in Russia, notably from Kirghiz which started to produce before the war. Exploratory work in connection with mercury recently has been widespread, stretching from the Donets area to Eastern Siberia. Despite the efforts to increase output of this strategic metal, Russia depends largely on imports from China and other United Nations. Chinese metal has been going to Russia for some time, and late in 1942 large quantities of mercury began moving to Russia from the United States. Exports from the United States were largely "reexports" or metal imported from Mexico, Canada, and Chile, although domestic metal made up part of the According to the Department of Commerce, shipments to Russia from the United States totaled nearly 21,000 flasks from October 1942 through February 1943.

<sup>&</sup>lt;sup>14</sup> Preller, G. S., The Place of Mercury in Peace and War: South African Min. and Eng. Jour., vol. 53 No. 2606, January 9, 1943, pp. 421–422.



# TIN

# By C. E. NIGHMAN AND J. B. UMHAU

# SUMMARY OUTLINE

	Page		Page
General summary	731	Consumption	738
Caliant statistics	732	Apparent consumption	738
Government ore purchases	733	Consumption by uses	738
Government tin smelter	733	Foreign trade	741
Conservation	734	Prices	743
Investigation of domestic tin deposits	735	Stocks	745
Domestic production	736	World aspects of tin industry	746
Mine output	736	World mine production	746
Smelter output	737	World smelter production	747
Secondary tin	737	International Tin-Control Scheme	748
		World consumption	748
		Review by countries	749

## GENERAL SUMMARY

An abrupt transition from an economy of abundance in tin to one of dearth marked the year 1942. In 4 months after the attack on Pearl Harbor the Japanese had added two-thirds of the world's tin resources and nearly three-quarters of the smelter capacity to the strategic metals assets of the Axis associates. There remained to what became known after January 1, 1942, as the United Nations a potential annual supply of only 80,000 to 90,000 long tons of virgin tin, a volume little greater than that consumed in the United States alone in 1940 (72,324 long tons) and much less than the 103,086 long tons used in the peak year 1941.

The terrific shock of the Japanese blitzkrieg in Malaya and in the Netherlands East Indies on the tin-consumption habits of the United States was fortunately cushioned by defensive measures undertaken coincident with the growth of an understanding of Japan's East Asia policies. Foremost among these measures were the inception of a stock-piling program and provisions for domestic smelting, with the

acquisition of ore supplies.

At the close of 1941 there were on hand 45,572 tons of ore and concentrates containing over 23,000 long tons of tin. Total stocks, excluding the 7,433 tons held by the Navy and Procurement Division, contained over 126,000 tons of tin as metal and in concentrates. Although 1942 opened with an abnormally large, immediately available stock, prospective future supplies were limited essentially to about one-half of Bolivia's raw-material output and to the Belgian Congo's metal—sources that at best could furnish scarcely 40 percent of the virgin tin consumed in 1941. Drastic steps thus had to be taken to maintain a safe position in tin. Immediate and severe restrictions were placed upon use; broad substitution programs and expanded reclamation schemes were instituted and were frequently revised or amended during the year but always in the direction of a tightening control. Exports, which were already governed by the

THE RESERVE OF THE PROPERTY OF

Export Control Act of July 1940, were likewise subjected to further restrictions.

As a result of control and conservation, nonessential uses were almost abandoned, there was widespread degradation in bearing metals, and a transition was being effected in the major consumption areas of solder and tin plate to tinless solders and to thin electrodeposited, chemically treated, and black plates, accompanied by enforced shrinkage in volumes. Although the effect of the shift to electrolytic tin plate, with its estimated 60-percent decrease in tin used compared with hot-dipped plate, was slight because of the difficulty in obtaining and installing a vast amount of new and specialized equipment, tin consumption showed an uninterrupted monthly decline ranging from 7,500 tons in January to 3,200 tons in December 1942, with the year's virgin tin consumption reduced to 56,000 tons or less than 55 percent of that used in 1941.

Imports of metal were at the lowest point in more than 20 years and were only 18 percent of the 1941 tonnage; although the total tin content of the ores imported increased by about 9 percent, the over-all drop totaled 66 percent. Of the 57,000 tons received, about 15,000 tons of metal and 8,000 tons (tin content) of ore belatedly arrived from Malaya, the Netherlands East Indies, and China. Total stocks Total stocks declined only 1.5 percent to the equivalent of 3% years' supply at the indicated consumption rate in the last quarter of 1942.

Salient statistics for tin in the United States, 1925-29 (average) and 1938-42

	1925-29 (average)	1938	1939	1940	1941	1942
Production—		1 1 1				
From domestic mines long tons From domestic smelters do	24	95	34	49 2 1, 391	56.3 2 1,839	1 6. 3 2 16. 168
From secondary sources do Imports for consumption:	30, 600	21,000	26,000	29, 700	37, 500	33, 900
Metal do Ore (tin content) do Exports (domestic and foreign) do	78, 009 175 1, 740	49, 699 (4) 3 205	70, 102 500 \$2, 105	124, 810 3, 000 3 2, 664	140, 873 28, 670 3 1, 094	26, 002 31, 212 409
Monthly price of Straits tin at New York: Highestcents per pound- Lowestdo	70. 67 39. 79	46. 23 36. 84	63. 50 45. 62	54. 54 45. 94	53. 35 50. 16	1
Average do do World production long tons Ratio—United States imports to world pro-	56. 64 163, 000	42. 26 163, 000	50. 18 176, 000	49. 82 236, 000	52. 01 245, 000	(5) 126, 000
ductionpercent_	48	30	40	54	69	45

Including tin content of ores used direct to make alloys.

Figures for 1938-41 cover foreign only; domestic not separately recorded.

Less than 1 ton.

5 Ceiling price 52 cents.

Maintenance of this relatively comfortable position—one that appears to have been paralleled in Great Britain—appears unlikely. A lengthy campaign for the recovery and rehabilitation of Far Eastern mines and reduction works is indicated. China is essentially isolated: production in Bolivia and Nigeria declined below 1941 levels and was not offset by the increase from the Belgian Congo, with little likelihood that an appreciable net increase may be expected in 1943, with all shipments subject to the shortage of bottoms and German submarine In Great Britain consumption is said to be held at the "austerity" level that lies at approximately 14,000 tons. It has been

TEN 733

THE REPORT OF THE PARTY OF THE

estimated that in the immediate pre-war years the U.S.S.R. apparently used about 15,000 tons annually, but its current actual needs are materially greater. (See section on Foreign Trade.) In the United States the principal remaining area of economy, which should be reached in 1943, lies in the substitution of thin electrodeposited and tinless plates for hot-dipped plate. However, the degree of substitution is limited by numerous factors, including the nature of the goods to be packed and the probable increasing volumes of plate and processed-food containers needed for Lend-Lease shipments and for overseas use, both military and civilian, all of which require higher-grade protective coatings than that serviceable for domestic With a probable consumption of around 50,000 tons in 1943 in this country, the total needs of the United States, Great Britain, and the U.S.S.R. seemingly exceed the maximum output of the United Nations that have an exportable surplus. Thus there may be no relaxation of controls; rather, more stringent enforcement and extensions are to be expected.

Controlled sales prices were effective throughout the year, in the United States at 52 cents per pound New York for Straits tin or equivalent grade, and in the United Kingdom at £275 for standard tin delivered buyers' works. Tin consumers have benefited greatly by these price-fixing policies. Under the revised contract with Bolivian producers the purchase price was set at 60 cents per pound at export ports, which has been estimated to be 62 cents or more New York. This represents an apparent subsidy of 10 cents per pound or approximately \$3,500,000 on the pig tin produced in the United States in

1942 or over \$5,150,000 based on imports from Bolivia.

## GOVERNMENT ORE PURCHASES

No sizable ore-purchasing contracts were concluded in 1942, but deliveries under earlier agreements continued. (See Foreign Trade—Imports.) One cargo believed to have contained about 2,000 tons of

tin was lost en route to the United States in May.

The original contract of November 4, 1940, with Bolivian producers was based upon a price of 48½ cents, c. i. f. New York, and contained a provision for price review at stated intervals. Pursuant thereto negotiations were undertaken, and as of June 30, 1942, the signing of an amended contract retroactive to January 1, effective through June 30, 1943, was announced. The price was raised to 60 cents per pound contained tin f. o. b. Chilean or Peruvian ports—an increase of nearly 30 percent, since freight and insurance fell to the account of the buyer. The contract also called for a minimum delivery of 1,500 tons per month and a maximum of 2,500 tons (tin content). Up to 20 percent of the shipments could range from 18 to 35 percent tin. Smelting charges were set at \$32.25, \$31.60, and \$30.40 per ton for the three classes of acceptable materials, with a sliding scale of deductions for impurities.

GOVERNMENT TIN SMELTER

Construction of the Federally financed tin smelter was begun in October 1941, and the first metal was poured April 5, 1942. The original plans called for capacity to treat the portion of Bolivian ores made available to the United States, that is, about 50,000 tons per

year or 18,000 tons of tin. Subsequent enlargements raised its capacity to about 90,000 tons or enough to treat the entire United Nations The total cost of the plant has been reported to be about ore supply. \$6,300,000.

A description of the smelter and methods of ore treatment, accompanied by flow sheets, has been published.1 The plant was designed to treat complex, low-grade as well as high-grade ores. Over-all recovery is said to exceed 98 percent. Two grades of tin are produced: Longhorn 3 Star, over 99.8 percent pure, and Longhorn 2 Star, which on a selling-price basis would assay between 99.00 and 99.75 percent.

In the metal trade here and abroad there has been much speculation concerning the post-war position of the Texas City smelter and an inclination to believe that it will remain a competitive factor in world Aside from any long-term ore-purchasing contract that may be made before the war's termination and the freedom of access to raw materials proposed under the Atlantic Charter, it occupies a strategic position geographically and with respect to fuel, hydrochloric acid, and power (somewhat offset, to be sure, by high unit labor costs). The additional advantages of a most modern and extremely flexible plant plus the accrued knowledge of efficient reduction processes for complex and off-grade ores endow the operating organization with considerable bargaining strength, especially in the low-grade or refractory ore field.

# CONSERVATION

The loss of the major supply sources before a stock pile of adequate dimensions could be accumulated necessitated the application of rigorous use controls, with corollary substitution and reclamation pro-These orders frequently were modified or amended to effect closer regulation and were extended through auxiliary limitation and conservation orders to stop lesser loopholes in the restraining program.

The final effect of the multitudinous orders cannot yet be evaluated exactly, but as shown under Consumption by Uses the program was highly effective in 1942. Estimates of potential savings indicated that roughly one-half would be derived from nearly complete prohibition of use, such as for foil and collapsible tubes, and the remainder through down-grading in tin content and substitutions. In the last field the displacement of metal by glass containers, largely as a result of the limitation placed on use of steel, was the most important factor and has been estimated to have been as great as 30 percent. Fiber containers have found increasing use and to some extent are expected to remain competitive in peacetime. Ordinary black plate cannot be expected to take the place of much tin plate because it lacks corrosion resistance, but chemically treated (bonderized) black plate, enameled or lacquered, is claimed to be suitable for many general line and some sanitary cans. It is believed that it may take care of more than one-eighth of the total container production in 1943.2 However, that product is still in an experimental stage, and its future application will depend in large measure on the availability of tin that has demonstrated value in food preservation. Only one plant was known to be operating in 1941, but it was expected that 18 to 20 bonderizing lines would be built in 1942.

Henderson, Charles B., The Longhorn Tin Smelter: Min. and Met., vol. 24, No. 436, April 1943, pp. 196–200. <sup>2</sup> Lippert, T. W., Food in Cans: Iron Age, vol. 149, No. 18, April 30, 1942, p. 30.

TIN 735

In the degradation area, the reduction in tin content of solders, extending to the tinless lead-silver solders, in bronzes and bearing and terne metals have effected pronounced economies in tin use. The greatest saving possibility in this field, owing to the huge quantities involved, lies in the reduction of thickness in tin-plate coating. By February 1942 this had been reduced from the customary 1.5 pounds per base box to the lowest practicable hot-dip limit of 1.25 pounds, with an appreciable resultant saving. However, the need of heavily coated tin plate for the large proportion of food packs intended for the armed forces and Lend-Lease so restricted the amount of tin available that it became imperative to employ an alternative method of coating that could provide the quantity of tin plate necessary for other consumers.

A metal coating of virtually any desired thickness can be electrodeposited. This method is not new, but its commercial application to tin plating on a plant scale is recent <sup>3</sup> and was still small in 1941 and 1942, amounting to only 2.85 and 3.4 percent, respectively, of standard coke tin-plate tonnage. To meet the expected demand—estimated to be as much as 40 percent of current tin-plate requirements—it was hoped to construct 26 or 27 electrolytic lines in 1942, but actual completion fell far behind the planned schedule owing to the inability to obtain the vast amounds of electric equipment and control apparatus

 $\mathbf{needed}.$ 

Electrolytic tin plate having only 0.1 pound per base box has been made experimentally and may serve for some purposes. In general, a coating weight of 0.5 pound is required for many packs under conservation regulations. There is a tendency, however, to believe that a heavier plate, 0.75 to 1.0 pound, eventually will be found more satis-

factory or necessary for the widest application.

The future economic position of thinly coated tin plate is not yet clear, as some time must elapse before it can be tested fully in practice. For numerous goods it would afford ample protection, and according to reports it can be soldered as well as the standard hot-dipped plate. In that respect and because it will withstand deformation—deep drawing or forming—without injury it is materially superior to bonderized lacquered plate and seemingly can be fabricated at much greater speeds. (See Review by Countries—Germany.) At present the 0.5-pound electrolytic plate has a price differential of 50 cents per base box in its favor. These and other advantages point to partial displacement of standard tin plate and chemically treated plate that some authorities have estimated as high as 40 to 50 percent.

# INVESTIGATION OF DOMESTIC TIN DEPOSITS

Continuing their endeavors to find workable tin deposits in the United States and Alaska, the Bureau of Mines and the Geological Survey extended earlier explorations, undertook several new projects, and published eight reports.

The Geological Survey made reconnaissance surveys in Alabama of pegmatites and in the Black Hills of South Dakota. Reports on these projects are not yet available. A field study of the Temescal district, Riverside County, Calif., was concluded. It is understood

<sup>&</sup>lt;sup>3</sup> The first plant for the plating of wide, continuous strip was erected by the Crucible Steel Co. at its Midland (Pa.) works in 1936. Shortly thereafter the Carnegie-Illinois Steel Co. installed an electrotinning line at Gary, Ind., and in 1941 the Crown Cork & Seal Co. put a line into operation at Baltimore, Md.

that the Metals Reserve Co. has approved the installation of machinery and that material for milling tests would be taken from open pits in the spring of 1943. Detailed studies of the Gorman district, northwest of Los Angeles, and mapping at Cima, San Bernardino

County, were carried out.

The Bureau of Mines and Geological Survey continued field studies on the tin resources of New Mexico. Preliminary reports indicate that some very small placer areas can probably be mined under present conditions but that the lode deposits are not sufficiently rich to be developed economically at this time. In March 1943 the Geological Survey published an areal geological map of the tin district in the Black Range in Catron and Sierra Counties, N. Mex., accompanied by a descriptive text prepared by Fries and Butler.

The Bureau of Mines conducted an exploration project that included drifting, crosscutting, and long-hole drilling at the Majuba Hill mine in Pershing County, Nev., and the Geological Survey made

a detailed study of the mine.

In Alaska, Geological Survey geologists studied and mapped tin placers in the Tozimoran, Morelock Creek, and Ruby-Long areas, all lying in the Yukon Basin region of the interior a considerable distance west of Fairbanks. The Bureau of Mines examined tin placers in the Buck-Creek-Potato Mountain areas at Cape Mountain near Tin City. In the Manley Hot Springs area near the junction of the Yukon and Tanana Rivers the Bureau of Mines examined tailings from early gold-placer operations. In July 1942 the Bureau of Mines began explorations in the Lost River tin area in western Seward Peninsula. The Geological Survey, in conjunction with Bureau of Mines engineers, made a supplementary examination. The Bureau's preliminary sampling in this area has indicated a large tonnage of low-grade tin-tungsten ore of about 0.8 percent tin and 0.25 percent WO<sub>3</sub>. This district appears to offer the best possibilities for domestic tin production; however, immediate development will depend on the ability to obtain clearance and ship space for transporting materials and supplies to this remote area. Bureau of Mines plans further exploration.

## DOMESTIC PRODUCTION

#### MINE OUTPUT

Domestic tin production dropped to 6.3 long tons, the lowest point in 9 years, owing to virtually complete loss of Alaskan output following commercial exhaustion of the Tin City placers. No lode tin was obtained in 1942.

The prospect for a sizable increase in the immediate future is far from bright. The total recorded mine production from the United States and Alaska in the past one-third of a century amounted only to 1,521 tons valued at about \$1,666,000,4 of which nearly 95 percent was furnished by Alaska. No consequential deposits were brought to light in the United States proper. Alaska has a small potential; but that, as far as is now known, is largely concentrated in low-grade and narrow lodes that require much machinery and equipment for large-scale production and concentration.

<sup>&</sup>lt;sup>4</sup> Data for 1910-38, inclusive, were published in Minerals Yearbook, 1939, p. 679.

THE PROPERTY OF THE PROPERTY O

			s, 1938–42, by	

	. * .		a 17		Long	tons		
	Year			Alaska	South Dakota	Other States 1	Total	Value
1938 1939		3.2		94 33	1.5	0.5	95 34	\$90,000 38,100
1940 1941 1942				46 46.8 2 2.8	2 1.4 1.4	8.1 2.1	49 56.3 26.3	54, 900 65, 600 2 7, 300
1714				- 2.0		2	- 0.0	1,000

 <sup>1939-40:</sup> Montana and New Mexico; 1941: Alabama, Montana, and New Mexico; 1942: Alabama,
 California, Nevada, and New Mexico.
 Subject to revision.

#### SMELTER OUTPUT

The major event of the year from a production standpoint was the revival of large-scale domestic smelting that had been dormant since Output for the first full month of operation (May) of the Longhorn smelter was 1,246 long tons, and it rose almost uninterruptedly to 2,343 tons in December, with a total for 1942 of 15,696 long tons, a little (65 tons) below the peak smelter output in 1920. Based upon the 2-month average for November-December 1942, however, production was at the annual rate of 28,000 tons. Shipments were 1,403 The 3 Star grade has received a favorable reception; the second or 2 Star grade, which is believed to assay about 99.5 percent tin, came on the market late in 1942.

Production from ores by privately owned smelters dropped 74 percent from the 1941 figure. Of the 472 long tons output, 243 tons (1941, 502 tons) appeared as pig tin and 229 tons (1941, 1,337 tons) in alloy form, principally solder. Companies reporting production in 1942 were the American Metal Co., American Smelting & Refining Co., Nassau Smelting & Refining Co., Phelps Dodge Refining Corpo-

ration, and Vulcan Detinning Co.

In 1942 one-quarter of the ore imports were from the Netherlands East Indies, which usually produced concentrates of approximately 72 percent tin content. Nearly all the remainder originated in Bolivia. The grade of these supplies is not available, but incomplete data on gross weight and tin content of the mine production give indicated grades for 1940, 1941, and 1942 of 51, 41, and 40 percent, respectively.<sup>5</sup>

## SECONDARY TIN

Total recovery of secondary tin declined about 10 percent from the record high level of 1941 to 33,900 long tons in 1942. Most of the so-called secondary tin (80 percent or more) is contained in copper-tin or lead-base alloys, from which it is rarely extracted as metal but remains as a circulating constituent. In addition to the decline in volume of re-treated materials, down-grading with respect to tin content in important alloys, such as solders, bearing metals, and bronzes, as a consequence of the conservation program, was beginning to affect the quantity of tin recovered. The principal source of metal and of tin chemicals is clean tin-plate clippings and used containers

<sup>&</sup>lt;sup>5</sup> These figures slightly understate the quality because the weight of sacks is included in the gross weight. The Metal Industry (London) of February 26, 1943, on the basis of grades of concentrates shipped in November 1942 and on the assumption that all the Patino-group product was delivered to England arrived at an average of about 36 percent for shipments to the United States.

treated at detinning plants. The quantity of tin reclaimed as metal by detinners rose about 4 percent to a new high of 4,700 long tons, but the tin content of chemicals declined 79 percent to a low of little more than 200 tons.

The collection of prepared, used tin cans has been highly disappointing—variously estimated to have been between a quarter and a third of the potential—but the amount of tin recovered jumped nearly 800 percent above the 1941 output of about 60 tons to over 530 tons in 1942. Although the weight of clippings treated dropped more than 15 percent from the 1941 level—a reflection of the restrictions placed on tin-plate manufacture—the amount of tin recovered receded only 6 percent to a little more than 4,160 long tons owing principally to the pronounced shift from chemical production as noted above. Further details will be found in the chapter on Secondary Metals—Nonferrous.

Secondary tin recovered in the United States, 1925-29 (average) and 1938-42

	Tin recove	ered at detin	ning plants	Tin recovered from all sources				
Year	As metal (long tons)	In chemi- cals (long	Total (long	As metal	In alloys and chemi-	To	tal	
	(long tons)	tons)	tons)	(long tons)	cals (long tons)	Long tons	Value	
1925-29 (average) 1938 1939 1940	900 2, 200 3, 600 3, 700	2,000 1,300 600 600	2, 900 3, 500 4, 200 4, 300	7,500 4,300 4,000 4,500	23, 100 16, 700 22, 000 25, 200	30, 600 21, 000 26, 000 29, 700	\$38, 034, 12 19, 284, 60 29, 276, 60 33, 102, 40	
19 <b>4</b> 1	•4, 500 4, 700	950 200	5, 450 4, 900	5, 300 5, 200	32, 200 28, 700	37, 500 33, 900	43, 722, 70 39, 434, 70	

# CONSUMPTION

## APPARENT CONSUMPTION

The apparent consumption of primary tin, calculated by adding smelter production to net imports, was 42,005 long tons in 1942 or roughly 30 percent of the 1941 record of 141,618 long tons. This method of reckoning consumption excludes all changes in metal stocks held by consumers and the Government, and in times of extraordinary movement, such as the period 1940–42, may present a highly distorted picture. Frequently, however, basic data for more accurate calculation are not available, hence apparent consumption statistics offer the only indicator of long-term trends. These data for 1910–38 were published in the Minerals Yearbook, 1939 (p. 680); those for 1938–42 follow.

## Apparent consumption of virgin tin, 1938-42, in long tons

1938	49, 494	1941	141.618
1939	67, 997	1942	42, 005
1940	123, 537		1-, 000

#### CONSUMPTION BY USES

The following tables show actual consumption of primary and secondary tin, as reported to the Bureau of Mines. Pronounced changes in the tin-consumption pattern arose during 1942 as a consequence of the metal's highly critical status. Tin plate retained its normal premier position, accounting for 51 percent of the consumption of virgin tin, although there was an absolute drop of 36 percent from

739

the 1941 record level. Solder that usually held second place, using about half as much tin (primary plus secondary) as tin plate, was displaced by bronze and brass that used 47 percent more primary and twice as much total tin as solder, with a new peak total consumption almost equal that of tin plate. Among the reasons for this shift were the recession in demand that followed cessation of automobile production at the end of 1941, the progressive down-grading in tin content in solders, and the continued expansion of armament output with the tremendous increase in the launchings of naval and merchant ships. Tin used for babbitt declined 42 percent, largely because of the decrease of approximately one-third in white-base antifriction-metals production and the substitution of lead-base for high-tin babbitts. The virtual elimination of tin for foil brought about a saving of approximately 3,700 tons or 87 percent of the 1941 Restrictions on the use of tin for collapsible tubes resulted in a drop of 75 percent compared with 1941. These uses in the immediate pre-war period, 1937-40, accounted for about 88 percent of virgin-tin consumption that averaged nearly 65,000 tons a year. In 1942 there was a relative rise to 91 percent but an absolute decline of 13,800 tons. A pronounced downward trend was in evidence in the remaining use fields, especially in tin oxide, galvanizing, and white metal, in which the enforced savings were roughly 90 percent of the preceding year's use. Changes in the application of secondary tin were much less pronounced, although alloy down-grading increased the proportions contained in solder, bronze, and brass. Secondary tin consumption in 1942 was 29,400 tons or 93 percent of that for the previous year, while the ratio of secondary to primary rose to 52 percent compared with the 24-percent peacetime (1935-39) average for which data are available.

Consumption of primary and secondary tin in the United States, 1938-42, in long tons

	1938	1939	1940	1941	1942
Stocks on hand January 1	25, 984	25, 260	29, 025	56, 999	<sup>2</sup> 67, 421
	61, 431	89, 018	128, 030	149, 123	65, 568
A vailable supplyStocks on hand December 31	87, 415	114, 278	157, 055	206, 122	132, 989
	25, 260	29, 025	56, 999	2 67, 421	8 43, 853
Total processed during year	62, 155	85, 253	100, 056	138, 701	89, 136
Intercompany transactions in scrap (tin content)	2, 122	2, 390	2, 190	2, 936	2, 547
Total consumed in manufacturingPlant losses	60, 033	82, 863	97, 866	135, 765	86, 589
	2 259	435	712	1, 070	902
Tin content of manufactured products	59, 774	82, 428	97, 154	134, 695	85, 687
PrimarySecondary	48, 116	4 66, 583	4 72, 324	4 103, 086	56, 288
	11, 658	15, 845	24, 830	31, 609	29, 399

 <sup>1938:</sup> Primary, 50,052; secondary, 1,983; terne, 787; scrap, 8,609.
 1939: Primary, 70,732; secondary, 4,976; terne, 1,171; scrap, 12,139.
 1940: Primary, 98,125; secondary, 5,409; terne, 1,086; scrap, 23,410.
 1941: Primary, 114,281; secondary, 6,879; terne, 1,851; scrap, 26,112; 1942: Primary, 33,126; secondary, 5,096; terne, 40,5 scrap, 26,941.
 Not including 2,700 tons in transit or in warehouses.
 Not including 2,700 tons in transit.
 Includes small tonnage of secondary pig tin.

The total tonnage of primary and secondary tin used was reduced 49,000 tons or 36 percent from the 1941 high and was only 4 percent above the 1937-40 average. The true effectiveness of the conservation program is to be evaluated, however, by the economy in virgin metal. Primary tin consumption was 47,000 tons or 45 percent less

# Consumption of tin in the United States, 1938-42, by finished products (tin content), in long tons

		1938			1939			1940			1941			1942	
Product	Primary	Second- ary	Total	Primary	Second- ary	Total	Primary	Second- ary	Total	Primary	Second- ary	Total	Primary	Second- ary	Total
Tin plate	3, 427 1, 738 2, 283 166 948 547 134 792 456 238	(1) 743 5, 208 1, 264 1, 598 35 (2) 910 (2) 444 978 213 19 44 202	23, 545 1, 007 12, 798 4, 157 3, 932 2, 283 2, 283 2, 1, 076 948 991 1, 112 792 669 257 434 578	1 36, 640 317 9, 578 3, 850 3, 385 3, 507 2, 165 2, 001 167 606 651 149 1, 028 1, 100 404 466 , 569	(1) 1, 137 7, 701 1, 598 3, 051 (2) 172 (3) 288 (2) 359 990 241 45 42 221	36, 640 1, 454 17, 279 5, 448 6, 436 3, 507 2, 337 2, 031 1, 139 1, 028 1, 341 449 508 790	1 38, 674 455 10, 222 4, 473 5, 444 3, 512 2, 455 1, 713 52 661 651 84 963 1, 000 353 953 659	(1) 1,058 8,797 3,173 9,216 (2) 265 330 (2) 506 1,048 91 11 83 252	38, 674 1, 513 10, 019 7, 646 14, 660 3, 512 2, 720 1, 713 2 382 661 1, 157 1, 132 963 1, 091 4, 036 1, 036 911	1 44, 854 917 18, 084 7, 495 10, 067 4, 233 3, 987 4, 292 280 1, 325 995 287 863 1, 526 42, 463 938	(1) 1, 129 10, 141 3, 104 13, 103 212 145 690 (2) 495 1, 528 1, 528 1, 528 1, 528 1, 528 1, 528 1, 528 1, 528 1, 528	44, 854 2, 046 28, 225 10, 599 23, 170 23, 170 2 325 1, 490 1, 815 967 2, 133 617 4 2, 561 1, 054	28, 522 339 7, 228 3, 195 10, 646 1, 048 2, 764 576 36 143 84 40 82 601 558 8 83 343	543 6, 696 2, 904 17, 009 51 251 210 18 47 1, 113 121 256 5 156 24	28, 522 882 13, 924 6, 099 27, 655 1, 099 3, 015 576 246 161 131 1, 153 82 722 814 \$239 367
	48, 116	11,658	59, 774	66, 583	15, 845	82, 428	72, 324	24, 830	97, 154	103, 086	31,609	134, 695	56, 288	29, 399	85, 687

Primary includes small tonnage of pig tin derived from detinning operations; Bureau of Mines not permitted to publish separate figures
 Small quantity included under "Miscellaneous."
 In 1937 pure tin tubing required 1,286 tons and tin-lined tubing 10 tons; not reported separately after 1937.
 Includes 454 tons of primary and 20 of secondary for Britannia ware and 64 tons of primary and 8 of secondary for pewter.
 Includes 9 tons of primary and 2 of secondary for Britannia ware and 2 tons of primary for pewter.

741

ノノスをはいるというという

than in 1941 and nearly 13 percent below the 1937-40 average. In Great Britain the savings goal had been set at about 50 percent of the average pre-war use, which probably has been reached, and Germany appears to have made greater reductions. Commenting on the United Nations tin situation, The Metal Bulletin of London said 6 "The fact is that tin is of far less importance as a war metal than anybody had suspected" and, with respect to common use, "to a greater extent than was realized at the time, the use of tin was of the nature of a semiluxury." The future of tin is not clear, but many of the displacements and substitutions forced upon the consuming industries by the exigencies of war, as indicated in the foregoing paragraphs, are likely to persist in the future.

# FOREIGN TRADE 7

The main constituents of the foreign trade of the United States until 1940 were the imports of pig tin and the exports of tin plate. In that year, owing to the newly initiated stock-piling program, metal imports reached a new high, which was then exceeded by the record importation of 141,000 tons in 1941. Total metal imports were 26,000 tons in 1942; but of that—the lowest figure in this century except in 1921 (24,197 long tons)—nearly 60 percent represented arrivals from Far Eastern countries that were cut off as sources early in the year.

In 1924-39, inclusive, the tin content of imported ores and concentrates had an annual range from less than 1 ton to 500 tons, with an average of only 150 tons. Ore imports attained an all-time record of 31,212 tons in 1942. Bolivia was the principal point of origin, furnishing 23,029 long tons or nearly 5 percent above its 1941 volume. Important because of the high quality and, for the near future, irreplaceable large share (26 percent) in imports were arrivals of 7,977 tons from the Netherlands East Indies. French Cameroun again supplied a small quantity-161 tons-and receipts from Mexico

dropped to 45 long tons.

The major tin-export item of the United States, as usual, was tin plate (including terneplate). In 1942 an all-time export record of 594,000 tons was set up—the United States became essentially the sole anti-Axis-world supplier.

Foreign trade of the United States in tin and tin concentrates, 1938-42

				Impo	orts		
Year		Tin	(metal)	Tin cone (tin co	Exports of tin (metal) <sup>1</sup> (long tons)		
			Long tons	Value	Long tons	Value	
1938 1939 1940 1941 1942			49, 699 70, 102 124, 810 140, 873 26, 002	\$44, 860, 324 70, 590, 764 128, 294, 410 149, 569, 328 28, 548, 018	(²) 500 3,000 28,670 31,212	\$298 418, 004 2, 687, 154 27, 671, 689 21, 422, 896	205 2, 105 2, 664 1, 094 * 165

Imported as pigs, bars, etc., and exported as such.
 Less than 1 ton.
 Also 244 tons of ingots, pigs, etc., as domestic exports accounted for in exports of miscellaneous tin manufactures.
 Figures for previous years not separately recorded.

<sup>&</sup>lt;sup>6</sup> The Metal Bulletin, No. 2751, December 11, 1942, p. 7.

<sup>7</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Tin 1 imported for consumption in the United States, 1941-42, by countries

Country	1	941	1942		
	Long tons	Value	Long tons	Value	
Australia Belgian Congo Brazil	250 11, 030	\$270, 956 10, 397, 351	10, 474 (²)	\$11, 153, 143	
British Malaya Canada China Hong Kong	104, 872 5 2, 845 4	112, 798, 138 5, 644 2, 702, 373 4, 248	7, 791 4 3, 625	156 8, 634, 882 1, 353 4, 017, 470	
Indochina, French Netherlands Indies Panama Portugal	487 17, 739	545, 814 18, 883, 180	3, 922 (²)	4, 485, 899 100	
United Kingdom 3	3, 641	3, 961, 624	87	159, 630 95, 385	
레일 등 등 나를 보면 하게 되고, 하다	140, 873	149, 569, 328	26, 002	28, 548, 018	

<sup>&</sup>lt;sup>1</sup> Bars, pigs, blocks, grain, granulated, or scrap, and alloys, chief value tin, n. s. p. f. <sup>2</sup> Less than <sup>1</sup> ton. <sup>3</sup> United Kingdom of Great Britain and Northern Ireland.

Foreign trade in tin plate, taggers tin, and terneplate in various forms, 1938-42, in long tons

Year	Tin-plate scrap		Tin-plate circles, strips, cob-	Waste- waste tin plate,	Tin plate, taggers tin, and terneplate		
	Imports	Exports	bles, etc., exports	exports	Imports	Exports	
1938	10, 444 12, 633 16, 615 22, 600	12, 495 10, 204 3, 536 180	4, 467 6, 552 4, 590 4, 952	7, 254 9, 132 6, 091 8, 321	109 99 137 109	161, 576 311, 016 383, 328 354, 940	
1942 1	24, 082		1, 333	3, 230	154	594, 095	

<sup>&</sup>lt;sup>1</sup> In addition, 15,153 long tons of terneplate clippings and scrap valued at \$474,374 were exported in 1940, 751 long tons valued at \$43,545 in 1941, and 76 long tons valued at \$4,350 in 1942; not separately classified before January 1, 1940.

Foreign trade in miscellaneous tin manufactures and tin compounds, 1938-42

Year		neous tin actures	Tin compounds (pounds)		
1938	Imports 1 \$19,453	Exports 2 \$2,064,515	Imports 865	Exports 172, 467	
1939 1940 1941 1942	20, 106 12, 429 2, 266 3 949	1, 098, 140 706, 425 1, 456, 353 591, 937	5 271 7, 224	204, 363 131, 019 137, 424 117, 191	

Of special interest was the change in destination of exports. tralia and New Zealand were sent 27 percent, a striking example of Lend-Lease. Canada took 11 percent and Iran 5 percent, a large part of which was terneplate. The surprising volume of 50,000 tons for the U. S. S. R., taken in conjunction with the reported British shipments of 26,000 tons of tin for about 18 months after the German attack in June 1941 and the large volumes delivered from European

Includes tin manufactures, n. s. p. f., tinfoil, tin powder, flitters, and metallics.
 Includes tin dross and tin-bearing scrap material other than tin-plate scrap.
 In addition, 505,346 pounds of tin dross, skimmings, and residues valued at \$63,978 were imported; not separately classified prior to January 1, 1942.

TIN 743

smelters in 1937–38, seem to indicate that Russia's wartime requirements exceed estimates of peacetime needs—contrary to experience in Canada, Great Britain, and the United States—and further suggest that its domestic production has not been as great as believed.<sup>8</sup>

Tin plate, terneplate (including long ternes), and taggers tin exported from the United States, 1941-42, by principal countries

	19	41	1942		
Country	Long tons	Value	Long tons	Value	
Africa: British East Africa Union of South Africa Other British South Africa Argentina. Australia Brazil British Malaya Canada. Chile China Colombia Cuba Egypt. Greece Hong Kong. India, British Indochina, French Iran. Mexico. Netherlands Indies New Zealand Palestine Paraguay. Peru Philippine Islands. Portugal Sweden. Switzerland Turkey. United Kingdom U. S. S. R. Uruguay Venezuela. Utherica. Unter Africa. United Kingdom U. S. S. R. Uruguay Venezuela. Uother countries	3, 695 23, 909 426 48, 081 50, 457 63, 506 13, 018 30, 023 8, 984 1, 811 3, 762 17, 271 9, 107 2, 537 6, 456 19 229 16, 888 5, 697 11, 739 145 1, 819 2, 843 6, 091 3, 390 52 28 4, 664 11, 340 1, 886 4, 836	\$386, 746 2, 758, 649 47, 402 47, 402 6, 431, 925 5, 883, 653 7, 697, 683 1, 459, 758 3, 443, 480 1, 906, 287 144, 665 2, 161, 000 965, 920 15, 283 257, 765 728, 044 1, 814 29, 554 2, 070, 121 728, 504 16, 197 223, 508 334, 254 694, 044 694, 916 5, 697 1, 265 3, 938 3, 967 698, 382 1, 423, 940 232, 968 577, 450	9, 167 31, 325 3, 915 56, 958 133, 029 37, 600 683 64, 146 10, 683 102 1, 260 14, 003 42, 264  17, 821  28, 384 14, 371 6, 491 5, 118 4, 535 3, 169  1, 758  2, 409 50, 058 12, 478 2, 254 15, 197	\$957, 91 3, 871, 71 490, 77 6, 938, 41 16, 526, 00 4, 495, 22 7, 255, 96 1, 277, 20 13, 49 173, 97 1, 807, 87 4, 285, 25 1, 907, 63 3, 050, 62 1, 853, 26 733, 84 2, 966, 70 566, 62 366, 96 278, 71 6, 366, 97 1, 537, 79 320, 86 1, 774, 25	

#### **PRICES**

Notwithstanding the actual spread of war to the four quarters of the globe and retention of only a third of the world production centers by the Allies, the control of tin-selling prices has been most effective. Immediately before the outbreak of the 1914-18 conflict, Grade A tin sold at 31.75 cents a pound, New York. When the United States entered that war in April 1917 the price had risen to 55.91 cents, and for a year before that date averaged 43.89 cents. In 1918 a maximum of \$1.10 was reached, and the year's average stood at 86.80 cents. August 1939, or just before the invasion of Poland, the average price was 48.76 cents, then rose sharply in September but receded to the October average of 55.25 cents, an average not reached in the following For the year August 1940-July 1941, the average was Effective August 16, 1941, the price of Straits tin was 51.45 cents. fixed at 52 cents a pound, New York, and has remained stationary at Domestic Longhorn 3 Star tin has commanded the same

<sup>8</sup> See Minerals Yearbook, 1940, pp. 700-701, and Minerals Yearbook, Review of 1940, p. 688.

price since it became available in April 1942. The 2 Star grade has been priced at 51.125 cents.

Dealings on the London Metal Exchange were suspended on December 9, 1941, under Control of Tin Order 3, which also established a basic price of £275 for 99 percent minimum tin (or £278.10 for 99.9 minimum), delivered consumers' works.

World prices became nonexistent when maximum prices were established in the major consuming countries and trading ceased on the world's principal tin markets, although small sales at exceptionally high prices have been reported from some countries.

Tin price data, 1925-29 (average) and 1938-42

	1925–29 (aver- age)	1938	1939	1940	1941	1942
Average prices:						
New York: 1					and the second	
Straits tincents per pound	56.64	42. 26	50.18	49.82	52.01	<sup>2</sup> 52.00
99.75-percent tin (English refined)do	(3)	42.07	4 47.84	5 48. 79	(6)	7 51, 628
99-percent tindo	55, 50	40.84	8 46. 35	\$ 49.98	<b>51. 26</b>	9 51, 12
London: 10						
Standard tin£ per long ton	254.6	189.6	226.3	256.6	11 261. 6	12 275. 0
Docents per pound 13	55.17	41.39	44.81	14 43, 87	14 47. 09	49.54
Premium allowed over standard:	444.7.74					
Straits£ per long ton	5.1	4.3	(3)	(3)	(3)	(8)
Bankado	6.9		(3)	(3) (3) (3)	(3)	(8)
Englishdo	7	1.3	(3)	(3)	(3)	(3)
Price indexes (1925-29 average = 100):	1111					1
Straits tin (New York)	100	75	89	88	92	9:
Copper (New York)	100	70	75	77	80	8
Lead (New York)	100	63	68	69	78	š
Nonferrous metals 15	100	74	79	82	85	š'
All commodities 15	100	80	79	80	89	10

American Metal Market.

Monthly price of Straits tin for prompt delivery in New York, 1940-42,1 in cents per pound 2

Month		1940				
Month	High	Low	Average	High	Low	Average
January February March April May June July August September October November December	48. 75 48. 00 49. 00 47. 50 55. 00 58. 00 52. 75 52. 62½ 51. 50 51. 87½ 51. 00 50. 20	50.05	45, 94 47, 09 46, 82 51, 48	50. 50 54. 25 52. 62½ 52. 50 52. 25 53. 12½ 55. 00 52. 00 52. 00 52. 00 52. 00	50. 10 50. 25 51. 25 51. 50 51. 75 52. 12½ 52. 50 52. 00 52. 00 52. 00 52. 00 52. 00	50. 16 51. 46 52. 06 51. 96 52. 16 52. 67 53. 33 52. 36 52. 00 52. 00
Year	58.00	44. 75	49.82	55.00	50.10	52.0

<sup>&</sup>lt;sup>1</sup> Ceiling price, 52 cents throughout 1942.

Maximum for Grade A, 99.8 percent or higher (includes Straits).

<sup>3</sup> Data not available.

<sup>10-</sup>month average. 7-month average.

January-August, nominal; September-December, 51.62 cents.

<sup>&</sup>lt;sup>7</sup> Maximum for Grade B, 99.75-99.79 percent, and Grade C, Cornish refined.

 <sup>8 9-</sup>month average.
 Maximum for Grade D, 99.0-99.74 percent.
 10 Metal Bulletin, London, as compiled by International Tin Research and Development Council.

<sup>11 11-</sup>month average.

In-Hondin average.
 British Government's maximum price.
 Conversion of British quotations into American money based upon average rates of exchange recorded by the Federal Reserve Board of the Treasury.
 Based upon free exchange rate.
 Based upon price indexes of U. S. Department of Labor.

<sup>&</sup>lt;sup>2</sup> Metal Statistics, 1942, pp. 425 and 427.

THE MANNEY THE WASHING

こうない かんしんかん おおおおおおおからん はっている

# STOCKS

The total year-end tin content of all stocks in the United States was only 1½ percent below that at the end of 1941, but owing to the great curtailment in consumption they were equivalent to more than 3 years' supply without future increments at the indicated rate of use in the last half year. The make-up, as a result of Government control of acquisition and distribution, was materially altered. Industry pig-tin stocks were depleted to approximately half those on hand at the beginning of the year, whereas those in Government hands increased 28 percent; and ore supply (tin content), after increasing rapidly in the first 6 months, showed a slight loss in the second half but ended the year at 37,210 long tons or 55 percent higher than at the beginning.

Consumer surveys continued by the Bureau of Mines throughout 1942 showed year-end industry primary tin stocks at plants to be 32,100 tons, of which 20,600 tons were at tin-plate mills. transit ceased to be important in the supply situation and was 78 tons at the end of December. Secondary pig tin moved rapidly to consumers whose year-end stocks were estimated to be about 300 tons.

Data on world stocks have not been published since June 1941. Since control of tin supplies by governments is effective throughout the world and their distribution is earmarked, it may be said that visible stocks, as usually defined, no longer exist, although actual metal held in what has taken the place of private warehouses is probably more than double the visible stock averages of 1939-40.

Stocks of virgin pig tin in the United States, December 31, 1938-42, in long tons

	1938	1939	1940	1941	1942
Location of stocks: Afloat to United States <sup>1</sup> At landings in New York <sup>1</sup> In licensed warehouses in New York <sup>1</sup>	4, 150 1, 837 3, 320	12, 663 2, 415 887	22, 627 6, 106 3, 073	<sup>2</sup> 15, 000 3, 129 371	<sup>2</sup> 900 (²)
Total visible supply <sup>1</sup>	9, 307 17, 851	15, 965 21, 111	31, 806 46, 574	18,500 5 6 56,922	<sup>2</sup> 900 7 31, 226
Total stocks on hand	27, 158	8 37, 976	8 78, 380	6 8 75, 422	8 32, 126

As reported by Commodity Exchange, Inc.

<sup>&</sup>lt;sup>2</sup> Estimated. 3 Not available.

As reported to the Bureau of Mines; does not include tin in process or secondary pig tin.
Includes 2,700 tons in transit in the United States and at other warehouses not contained in figures above for "at landings" and "in licensed warehouses."

<sup>7</sup> Includes 78 tons in transit and 84 tons held by jobbers.
8 Exclusive of Government purchases delivered for stock piling.

Visible stocks of tin in the world and in the United States at end of each month, 1925-29 (average) and 1938-42, in long tons 1

Month	1925 (aver	5-29 rage)	19	38	19	39	19	40	19	41	194	12 <b>2</b>
	World <sup>1</sup>	U.S.	World	U.S.	World <sup>1</sup>	U.S.	World <sup>1</sup>	U.S.	World <sup>1</sup>	U.S.	World	U.S.
January February March March April May June July August September October November December	18, 912 19, 620 18, 312 17, 765 19, 085 18, 250 18, 164 18, 339 18, 317 18, 356 19, 058 20, 557	2, 803 2, 189 2, 384 2, 390	29, 002 34, 872 35, 359 33, 051 35, 844 39, 119 41, 701 40, 544	4, 500 5, 060	40, 035 37, 788 37, 224 33, 715 30, 039 29, 615 26, 338	5, 486 5, 806 3, 385 3, 387 4, 388	33, 148 32, 339 32, 149 30, 562 31, 869 38, 736 38, 040 39, 450 40, 631 40, 046	1, 749 2, 078 2, 635 2, 964 3, 677 5, 300 6, 567 6, 583 9, 438 6, 623 4, 362 9, 179	44, 107 39, 971 38, 788 40, 777 38, 600 (2) (2) (2) (2) (2) (2)	7, 489 5, 195 5, 016 7, 205	(2)	(2)
Average	18, 744	<b>2</b> , 573	36, 149	4, 617	34, 962	4, 130	36, 435	5, 096	(2)	4, 502	)	

Metal Statistics, 1942, pp. 417 and 419. In this table figures for world stocks, 1938-41, include carry-over in the Straits Settlements (on lighters and warrants) and carry-over at principal European smelters.
 Publication of statistics suspended owing to war.

## WORLD ASPECTS OF TIN INDUSTRY

## WORLD MINE PRODUCTION

Official statistics from all tin-producing countries have not been available since 1939, but it appears probable that production in 1942 was not much more than half that of 1941. Production in countries accessible to the Allies was somewhat below expectations, especially in Bolivia, where a decline of about 9 percent from the 1941 output was reported. In the East, notwithstanding Japanese assertions, output from Burma, British Malaya, and Netherlands Indies was probably only a small fraction of normal. In Thailand, too, there was some interference with mining, as well as plant damage, and China's inaccessibility doubtless held production low.

World mine production of tin (content of ore), 1925-29 (average) and 1938-42, by countries, in long tons

[Compiled by B. B. Waldbauer]

Country	1925–29 (average)	1938	1939	1940	1941	1942
Restricted production:						
Belgian Congo	967	8,820	8,964	12, 482	16,006	16, 844
Bolivia (exports)	37, 169	25, 484	27, 211	37, 940		38, 29
Indochina	691	1, 599	1,470	2, 098	42, 199 1 1, 430	1 1, 40
Malay States:	001	1,000	1, 410	2,050	- 1, 400	- 1, 40
Federated	54,606	41,206	49, 525	n i		
Unfederated	2, 206	2,041	1, 994	85, 384	1 78, 000	1 15, 000
Straits Settlements		114	206	00,004	- 10,000	- 10,00
Netherlands Indies	33, 266	27, 299	27, 755	43, 193	1 51,000	1 10,000
		8, 977	9, 427	12, 012	1 15, 000	1 12, 500
Nigeria Thailand (Siam)	8, 204	14, 704	2 17, 325	17, 447	1 16, 250	1 12, 000
Total signature countries	145 450	100 044				<u>-</u>
Total signatory countries	145, 453	130, 244	143, 877	210, 556	220, 000	106, 000
Unrestricted production:						
Argentina	32	1,886	1,655	1,481	921	1 700
Australia	2,830	3, 329	3,500	(3)	(3)	1 3, 00
Burma	2,228	7, 100	8,536	ı 5, 500	(3) (3) (3)	(3)
Cameroun, French		242	255	(3)	(3)	(3)
China	27,085	<sup>2</sup> 11, 605	<sup>2</sup> 10, 422	<sup>2</sup> 6, 249	17,000	ı 7, 000
Germany	98	i 300	1 300	(3)	(3)	(3)
Italy		271	229	(3)	(3)	(3) (3) (3)
Japan	625	2, 186	1 1, 700	(3)	(3)	(3)

See footnotes at end of table.

World mine production of tin (content of ore), 1925-29 (average) and 1938-42, by countries, in long tons—Continued

[Compiled by B. B. Waldbauer]

365 (3) (3) 2,142 (3)	212 (³) 45 2,261	(3) 72 (3)	(3)	289	040		
(3) (3) 2, 142 (3)	(3) 45 2, 261	(3) 72 (3)	(3)	289			Unrestricted production—Continued.
(3) 2, 142 (3)	45 2, 261	72			249	2	Mexico
2, 142 (³)	2, 261			(3)	27	4	Morocco, French
(3)				47	103		Peru
	/2\		1,721	1,486	1,037	625	Portugal 4
(0)	(*)	8 (3)	8	7	4	5	Portuguese East Africa
							Rhodesia:
(3)	(3)	(3) (3)	(3)		3		Northern
162	239		(3)	451	267	15	Southern
(3)	(3)	(3) (3)	(3)	1 40			Somaliland, Italian
(3)	120	137	137		164	149	
287							
(3)							
(3) (3) 6 412							Swaznand
/35							
6 412							Uganda
6 1, 400						1,174	
1,400				1,000			
<u> </u>			49	34	95	24	United States
20,000	25,000	25,000 25,0	25, 000	32,000	32, 325	17, 957	Total nonsignatory countries
126,000	245 000	236,000 245,0	236,000	176,000	163, 000	163, 000	Grand total
	83 (3) 251 (3) 5 460 1 1,600 56 25,000	100 103 258 (3) 518 1,560 49 25,000 25,000 25,000	100 103 258 (3) 518 1, 560 49 25, 000				South-West Africa Spain Swaziland Tanganyika Uganda Union of South Africa United Kingdom 4 United States Total nonsignatory countries

#### WORLD SMELTER PRODUCTION

Production from the world's smelters is likewise unknown, but it suffered severely when the British and Hollanders were forced from The Penang smelter, however, is believed to their Asiatic holdings. have continued in operation. Chinese inland smelter production doubtless did not exceed 7,000 or 8,000 tons; Japanese plants probably were operated at capacity. A small electric smelter was in operation in British Columbia. In less than 9 months, the Texas City smelter produced 15,696 long tons of tin; however, at the end of the year the annual production rate had risen to over 28,000 tons.

World smelter production of tin, 1925-29 (average) and 1938-42, by countries, in long tons

[Compiled by B. B. Waldbauer]

Country	1925–29 (average)	1938	1939	1940	1941	1942
Argentina		2, 093	1,080	881	768	1 900
Australia	2,952	3, 229	3,300	(2)	1 5, 000	1 3, 000
Belgian Congo		2, 283	2, 124	7,832	15, 000	1 14, 400
Belgium 1	720	<sup>3</sup> 6, 700	<sup>3</sup> 3, 100	(2)	(2)	(2)
British Malaya Canada.	4 88, 855	4 63, 746	4 81, 536	<sup>3</sup> 126, 945	<sup>1</sup> 125, 000 29	1 10, 000 56 <b>0</b>
China	5 7, 080	11,200	10,850	1 13, 000	1 10, 000	17,000
Germany 6	3, 444	3,000	1 3 3, 600	(2)	(2)	(2)
Italy	-,	271	229	(2) (2)	(2)	(2)
Japan	606	1,900	1 3 2,000	ı` 1,800	(2)	1 4,000
Mexico	(2)	(2) <sup>'</sup>	. 90	116	150	(2)
Netherlands	7 1,000	1 26, 400	1 14, 600	2, 967	(2)	(2)
Netherlands Indies 5	14,749	7, 207	13, 941	22, 035	1 23, 000	1 5,000
Norway	(2)	254	283	(2) <sup>'</sup>	(2)	(2)
Portugal	` 82	39	. 30	781	1, <b>4</b> 81	1 2,000
Thailand (Siam)	9 113		(2)	(2)	(2)	(2)
Union of South Africa	1			(2)	10 143	10 268
United Kingdom 1	45, 800	36, 200	37, 400	(2) (2) (2)	40, 000	30,000
United States				11 1, 391	11 1, 839	11 16, 168
	165,000	164, 500	174, 100	(2)	(2)	(2)

<sup>3</sup> Yearbook of American Bureau of Metal Statistics. 1 Estimated. 2 Data not available.

<sup>3</sup> Estimate included in total.

<sup>•</sup> ESSUMATE.

4 Restricted production basis from 1934-36, inclusive.

5 January to November, inclusive.

<sup>6</sup> January to October, inclusive.

<sup>\*</sup> Exports plus difference between carry-over at end and beginning of year.

Exports. 6 Includes production of some secondary tin. 7 Estimated production in 1929.

A verage for 1926-27. 6 Average for 1926-28. 10 Fiscal year ended July 31 of year stated. 11 Including tin content of ores used direct to make alloys.

#### INTERNATIONAL TIN-CONTROL SCHEME

The third International Tin-Control Scheme expired December 31, 1941. A fourth was recommended for adoption in December 1941, but the outbreak of war in the Pacific and objections to proposed quotas by some of the participants delayed acceptance until September 9. 1942 (retroactive to January 1, 1942), when the agreement was formally ratified by representatives of the countries participating in the preceding Scheme, except Thailand and French Indochina.9 The standard tonnages in the accepted form were those contained in the proposed text, except for the omission of Thailand. They vary considerably from the earlier bases, as actual experience with virtually unlimited production (130 percent of standard tonnage) for a year from July 1940 showed that some of the signatories could not attain the high quotas provided. Pending acceptance of the fourth agreement, tentative quotas had been set at 105 percent of the revised standard tonnages and were retained as far as known through 1942. The new agreement is to run for at least 5 years; the United States will have two representatives (nonvoting), one selected by the Government and the other a consumer representative, and there will be an additional representative for consuming countries other than the United States. Under the present war conditions the control agreement is purely nominal, but it does provide a continuing possibility of exercising some production control in the event of future wide fluctuation in demand.

In June 1938 a Buffer Pool was established, with the aim of stabilizing the price between £200 and £230. A stock of 15,512 tons was created between August 1, 1938, and July 1939; total purchases and sales were 66,428 long tons. In April 1942 it was decided to liquidate the remaining stock and complete the distribution of credit balances. The first distribution, in which all seven of the signatories to the Third Control Scheme participated, was made between November 1939 and February 1940 and amounted to £1,010,000. The final distribution of June–July 1942 amounted to nearly £2,285,000. In addition, balances to Thailand (£216,300) and to Indochina (£37,000) could not be paid because of legal difficulties arising under the Trading with the Enemy Act. It has been suggested that these funds be redistributed to the other parties to the Pool. The average realization without interest and before London overhead expense was £226.16.5 and the average distribution to the end of 1942 was £229.9.9.10

### WORLD CONSUMPTION

Owing to the lack of basic statistical data for the past 3 or more years, the table of apparent world consumption is omitted from this review. Assuming the usual relationship between domestic and world consumption, the last named probably was about 125,000 tons in 1942 and may be expected to fall below that in 1943.

American Metal Market, vol. 49, No. 251, December 31, 1942, p. 5, gives the full text of the agreement. The full report of the Executive was printed in American Metal Market, vol. 50, No. 96, May 20, 1943, pp. 5-6.

TUN 749

いところののは一般を見る 一日 とのなる 大いないこと

The state of the s

### REVIEW BY COUNTRIES

Argentina.—Operations at the Pirquetas mine and the Pircas Creek placer continued during 1942, but with a smaller output than in 1941. The Buenos Aires smelter, which had treated most of the ore, could not produce enough tin to satisfy demands because of the contraction

in ore supply, and some tin was imported.

Australia.—Production in 1942 has been estimated at 3,000 tons. Before the war, consumption of tin in Australia (including New Zealand) averaged 2,000 tons annually, and with the production of 3,000 to 4,000 tons there had been an exportable surplus. However, war needs have been greater than available supplies, and it was necessary to acquire a small tonnage from the United States for use in New Zealand. In 1943 mine output is expected to reach 4,000 tons but may not be realized owing to labor shortage and delays in obtaining dredges and other mining equipment. Some aid has been furnished through Lend-Lease, which also made available funds for canning equipment to expand production to provide food for American troops in Australia and New Zealand.

Effective May 1, 1942, the price of tin was set at £A371 per long ton, an increase of £A51. To encourage production from low-grade sources, it has been proposed to establish a pool for developing low-grade deposits by allocating £A10 per ton. The increased price of tin brought about a rise in output by small producers in 1942, but the lack of labor and continued withdrawal of competent men nullified

the efforts of larger companies to expand their yield.

Belgian Congo.—The United States imported 10,474 tons of pig tin from the Belgian Congo during 1942 (11,030 tons in 1941). A sizable tonnage of pig tin was lost at sea through enemy action. Some cassiterite containing about 1,670 tons of tin mined in 1942 was to have been shipped to England. Mine output for 1943 has been estimated at 21,530 tons of tin, although it may not be reached because of a developing water shortage. The entire 1943 output of pig tin and cassiterite will be shipped to the United States. The Belgian Minister of Colonies is reported to have stated that by 1945 the Belgian Congo would be able to produce 35,000 tons of metallic tin annually.

Bolivia.—The tin content of concentrates exported from Bolivia declined 8 percent from the 42,199-ton level of 1941 to 38,293 long tons in 1942, or 22 percent below the permissible quota of 49,106 tons (105 percent of standard) allowed under the Control Scheme. The United States was the destination of 53 percent of the 1942 export, and the remainder went to Great Britain. Inability to approach the quota was attributable to labor unrest that culminated in serious disorders at the end of the year, to a decline in grade of ore—the Patino Enterprises reported 2.83 percent in 1941 and 2.55 percent in 1942—accompanied by lower mill recoveries, and to general shortages in labor, equipment, and supplies. In an attempt to halt the downward production trend and if possible reverse it, financial aid and the assistance of numerous specialists were furnished by the United States.

<sup>11</sup> Tin, Belgian Congo: January 1943, p. 2.

At the request of the Bolivian Government a labor commission that worked jointly with Bolivian officials made a study of working conditions, wages, and security of workers, especially among miners. The commission submitted its report with recommendations to the Bolivian Government in March 1943, but its contents had not been disclosed in this country when this review was written. American technologists began studies of mining and metallurgical practices with the object of expanding output, especially at the smaller mines, and of improving the ore-dressing methods that are said to make recoveries of only about 50 percent at the plants of small and medium producers and of 72 to 80 percent by the major groups. To improve economic conditions and stimulate strategic materials output, the Bolivian Development Corporation was set up December 29, 1942, as a cooperative undertaking of the Bolivian Government and the Export-Import Bank, the latter furnishing credits of \$15,500,000 out of a total capital of \$26,000,000.

British Malaya.—The Japanese conquest of the Malay Peninsula was completed by the fall of Singapore on February 15, 1942. In 1941 about 68 percent of the output of the mines in the Federated Malay States came from European-owned and about 30 percent from Chinese-owned mines. About one-half of the production was obtained by dredging, and the bulk of the remainder by pumping, with small amounts from hydraulicking, open-cuts, and underground workings. Late in December 1941 the Government ordered the mine operators to destroy their properties. Annual reports of the principal British-owned companies indicate that many of them had sunk their dredges, destroyed power plants, and flooded their open-cast workings, but there is some doubt that the damage inflicted could have been as great as contemplated because of the rapid movement of the Japanese

 $\mathbf{forces}$ 

Burma.—The plant of Mawchi Mines, Ltd., was immobilized, and the property at Pazaung on the Salween River was evacuated under military orders on April 5, 1942. Lashio, the terminus of the Burma Road, was occupied by the Japanese April 29. The important tin mine area in lower Burma, south of Moulmein in the Tavoy and

Mergui districts, was also gained by the Japanese.

Canada:—Although occurrences of tin have been reported from numerous localities in Canada, none has commercial importance. At present, however, Grade A tin is being produced at the Sullivan mine of the Consolidated Mining & Smelting Co. of Canada, Ltd., near Trail, British Columbia. At that mine cassiterite was discovered in the tailings from the lead-zinc concentrator in 1925, but as the amount of tin was small it was then considered only of academic interest. Subsequent and extensive research lead to the development of a satisfactory recovery process that is described in Canadian Institute of Mining and Metallurgy Bulletin 356, December 1941 (pp. 611–622). On March 1, 1941, a plant was put into operation, and in April 1942 an electric smelter that produced 560 tons of pigtin in 1942.

The discovery of a high-grade ore body carrying cassiterite and stannite in the Woolsey mine in the Revelstoke district, British

Columbia, was reported.

In Manitoba the occurrence of tin has been known for many years. Great interest was aroused in the Rush Lake-Bird River district,

751.TIN

where a sample taken in 1940 had shown 0.3 percent tin. The Canadian Department of Mines and Resources examined what was believed to be the best cassiterite showing and recently issued a report.12 Reviewing the current and earlier field work the writer concluded that "There is no known tin occurrence of commercial dimensions in Manitoba that contains sufficient tin to justify its recovery even under the stress of wartime requirements."

China.—Authentic statistical data on tin have been available only irregularly in recent years, but various estimates indicate that Chinese production rose from about 9,000 metric tons in 1935 to approximately 13,000 tons in 1940. The virtual isolation of southwestern China, serious inflation, the migration of workers to agricultural employment inducing a labor shortage, high wage levels, extremely high fuel and transportation costs, and inability to bring in supplies and equipment severely retarded development and production so that output in Yunnan fell to about 5,000 tons and that of China to roughly 7,000 tons in 1941, according to official figures.<sup>13</sup> The final closing of the Burma Road and some fighting along the Yunnan borders would have tended to hold down production in 1942, but the National Resources Commission has just reported that in Yunnan there was in 1942 a gain of about 1,000 tons over 1941;<sup>14</sup> total Chinese production may therefore have exceeded 7,000 tons. Although tin has not been mentioned specifically, it is believed a small tonnage was exported to Russia over the Northwest Highway in 1942, and a small amount has been flown out to India. Immediately after the attack on Pearl Harbor redoubled attempts were made to expedite the movement of tin over the Burma Road, and although a substantial amount did get through to the United States the unexpectedly early fall of Rangoon and evacuation of Burma resulted in the loss of large quantities of metal.

Germany.—Early in 1941 some authorities believed that Germany faced an immediate and dire tin shortage, a shortage more serious than in petroleum and food. 15 It is not yet, however, evident that a lack of tin has caused any pronounced decline in its war effort, because Germany has been and is waging a major war with very little supply. The German reserve position was probably better and the amount of loot greater than assumed. Civilian use of scarce materials had long since been reduced to negligible volume, and the use of substitutes even in essential industries had been strictly enforced. tensive salvage campaigns had brought out much metal. At the same time, some new supply apparently reached Germany. Although the sinkings of several tin-carrying ships have been announced, it has been reported that since the fall of 1942 at least 26 vessels have run the

It has been claimed that great progress has been made in the substitution of bonderized lacquered plate for tin plate.<sup>16</sup> During the First World War considerable experience had been gained, presumably for general line cans, and much experimentation followed to determine the best basic coating, type of lacquer, and kind of plate to be used.

blockade from Kobe to Bordeaux.

Bateman, J. D., Tin in Manitoba: Canadian Min. Jour., vol. 64, No. 5, May 1943, pp. 273-278.
 Metal Bulletin (London), 1941 Chinese Output Down: December 22, 1942, No. 2754, p. 7.
 Foreign Commerce Weekly, May 22, 1943, vol. 11, No. 8, p. 34.
 Tin, Tin and Germany's War Effort: April 1941, pp. 3-4; quoted in part in Minerals Yearbook, 1941,

It was also determined that bonderizing and lacquering should be carried out by the can maker rather than by the rolling mill to avoid damage to surface in transport and handling. Body seams of this type of can cannot be soldered, and recourse was had to welding, for which an automatic welder was developed. This system is said to save incidentally 330 pounds of steel per 100,000 cans because of a smaller overlap.

A commercial-scale plant was erected in 1938. Bonderizing and lacquering were carried out in separate plants, but subsequently both were combined into a single unit. The article describes one operating plant that has a capacity of 5,000 to 6,000 cans an hour. Other plants

appear to be operating.

The bonderized-lacquered cans are said to be satisfactory for meats and vegetable packs and for some but not all fruits. Future development is a questlon of lacquers with further possibilities if a scheme of full welding, including the ends, can be devised.

Italy.—The output of tin in Italy was about 300 tons in 1942. The only productive tin mines are near Villacidro, Cagliari, Sardinia, where a concentrating mill of 50 tons daily capacity is said to be producing

1 ton of high-grade concentrate a day.

Japan.—The Japanese policy of enslaving subject peoples has been extended to cover mineral and other wealth as well. In December 1942 Premier Tojo declared that Japan must win each decisive battle and make every effort to retain control of all natural resources gained in the initial victories. Such avowal of a determined policy of exploitation of subjugated territories was confirmed by the repeated reports, mostly originating from Japanese sources, that many tin mines and some smelters were again in full operation. Nevertheless. it appears improbable that ore production would have greatly exceeded smelter capacity, which when last reported was about 5,000 tons in Japan. So far as is known, Indochina's small reduction works were not harmed, reports of the destruction of the Penang smelter were conflicting, and the Hong Kong smelters were probably in large measure available. Japan had then access to ample smelting facilities to meet its apparent requirements of about 12,000 tons annually. The extremely rapid rise in pre-war apparent consumption points toward a large wartime accumulation; and if, as reported, high-grade concentrates are flowing to Japan from Malaya and the Netherlands Indies, its internal smelting capacity would be enlarged without addition to plant. Thus the Japanese Empire has not only obtained self-sufficiency in tin but may be establishing a long-term reserve against any eventualities, and any excessive accumulation would present an economic threat to post-war tin-market stability.

Some tin, probably several thousand tons, was shipped to Germany and Italy during 1942 as the British have disclosed the interception,

sinking, or scuttling of ships carrying tin cargoes.

Mexico.—Mine production of tin in Mexico was 365 long tons in 1942 compared with 212 tons in 1941. Most of the 1942 production was utilized within Mexico, as 93 long tons were exported (108 in 1941). The price of tin was extremely high, being quoted at about \$1.25 (U. S. currency) per pound. This led to the relatively marked increase in production and a drop in exports.

A new smelter designed for Metalurgica de Mexico, S. A., to treat tin, mercury, and antimony ores was completed in May 1942 at

Tlalnepantla near Mexico City.

TUN 753

人名 人名英格兰斯 人名英格兰斯 人名英格兰斯

できる とうない 大きの 大学 大学 からから できる いまかい いかかい と

Netherlands East Indies.—Authentic information is lacking on the quantity of tin produced in the Netherlands Indies during the early part of 1942 before they fell into Japanese hands. However, 3,922 tons of pig tin and 7,977 tons of ore (tin content) reached the United States from that source during 1942. It has not been reported what portion of this was derived from stocks. The Japanese announced in the latter part of 1942 that the tin mines at Banka, Singkep, and Billiton had resumed operations, but it is doubtful that any great volume has been produced.

Nigeria.—Nigeria failed to meet expectations in 1942, as mine output was only 12,500 tons of tin or 7 percent below the permissible quota of 16,135 tons under the new Tin-Control Scheme. This was a particularly disappointing result, as the producers had been requested by the Government to increase output to the limit, and several companies reported that they were "picking the eyes out" of their deposits, regardless of the future. In some quarters the falling off in production was attributed to the Government restriction on prospecting, which

has not yet been lifted.

Production, including stocks on hand and in transit, was taken over by the Ministry of Supply, December 9, 1941, but freight and insurance remained for account of the seller until July 1942. After long negotiations, the price to be paid Nigerian producers has been tentatively established. It is based upon costs and profits for the year ended August 31, 1939, or the average of the 3 years ended on that date, with adjustments for increases or decreases from those of the base period. Freight, marine, and war-risk insurance will no longer be paid by the sellers. It is understood that the new basis is £217 per ton (the 3-year average price for the period ended August 31, 1939) and that £150 per ton will be paid at port of shipment, with final settlement after assay in England.

Wages paid native workers have been increased as a result of Government intervention. Compulsory labor regulations have been introduced. It was said that more than 14,000 laborers are now working under these regulations and that the total force exceeds 70,000. Production plans call for an annual output of 20,000 tons if labor can

be found.

Portugal.—Portuguese smelters have flourished in a small way owing to wartime conditions, as ore formerly exported is now treated within the country. A Metal Control Commission has been set up to control production and distribution and to fix prices. All tin must be offered to the Commission at a fixed price. Of the tin purchased, 25 percent is to be reserved for use in Portugal and the remainder is to be distributed between Axis and United Nations purchasers. Germany was offering very high prices for Portuguese tin early in 1942.

Spain.—Although it has been believed that Spain has sold tin to Germany the volume appears to have been small owing to the generally short supply. According to the Metal Bulletin of February 12, 1943, Spain had to import about 90 percent of its needs or 1,000 to 1,500

tons a year.

Union of South Africa.—The Zaaiplaats Tin Mining Co., Ltd., treated 42,690 tons of ore and recovered 182 long tons of concentrates in the year ended July 31, 1942, compared to 194 in the previous year. From its own and custom ores, the smelter produced more than 268 tons of pig tin in 1942 (143 tons in 1941). A third furnace has been added to the plant.

South-West Africa.—In the fall of 1942, discovery of a promising tin prospect at Kaokoveld, South-West Africa, was announced. The district lies in the northeastern part of the mandated territory near the Bechuanaland Protectorate border and is southwest of Caprivi

Zipfel.

United Kingdom.—The consumption of primary tin in the United Kingdom has been brought down to around 14,000 tons annually compared with 30,000 tons in 1941 and 29,225 tons in 1940. Rigid control, under strict Government allocation, is exercised, and new measures for economizing in tin consumption are constantly coming forward. The tin-plate industry normally consumes about 40 percent of the tin used in the United Kingdom. The Welsh tin-plate industry operated at a very low level; permits to purchase tin plate were small, and most of the orders were for plate for lacquering. The electrolytic tin-plate process has been under investigation, but reaction appears unfavorable to the use of the thinly coated plate. Nevertheless, at the year end a small electrolytic unit was nearing completion.

Imports of ore from Bolivia and Nigeria apparently were lower in 1942 but were, however, adequate to meet smelter requirements. Trade journals generally believe that the tin position is comfortable

in the United Kingdom.

U. S. S. R.—Russia has been almost wholly dependent on imports for its requirements, as its domestic production probably does not exceed 2,000 tons annually. It is believed that some tin was received from China during 1942; whether any was acquired from Japanese sources is unknown. Since June 1941 Great Britain has sent 26,000 tons of tin to Russia. It is unknown whether any was lost at sea from enemy action. According to The Metal Bulletin (London), "Japan might conceivably ship tin to Russia, who would be an equally ready buyer. At the moment, however, we have no information as to what trade, if any, is still going on between Russia and Japan." It has been reported, however, that Japan is selling rubber and other products to Russia.

<sup>17</sup> The Metal Bulletin, Japan and Tin: No. 2733, October 9, 1942, p. 6.

# **ARSENIC**

## By Allan F. Matthews

#### SUMMARY OUTLINE

	Page		Page
General statement	755	Consumption and uses	757
Salient statistics	755	Stocks	759
Domestic production	755	Prices	759
Foreign trade	756	World aspects	759

## GENERAL STATEMENT

Domestic production of white arsenic in 1942 fell 12 percent below the 1941 record, but this decrease was more than balanced by a 59-percent increase in imports, permitting consumption to advance 5 percent. More than a third of the new supply of arsenic in the United States in 1942 came from Mexico. The quoted price of white arsenic remained at 4 cents a pound throughout 1942. Arsenic was placed under allocation control by the War Production Board May 22, 1942 (Order M-152).

Salient statistics for white arsenic in the United States, 1938-42

	1938	1939	1940	1941	1942
Production short ton Imports for consumption do. Exports (by producers only) do. Consumption do. Average value of producers' sales:  Crude cents per poun Refined do.	14, 238 2, 267 1 25, 100 d 1. 4	22, 341 14, 674 3, 178 1 33, 900 1. 0 1. 4	24, 983 9, 929 1, 639 1 31, 600 1. 1 1. 5	32, 481 10, 292 1, 616 40, 442 1. 5 2. 2	28, 681 16, 350 305 42, 411 2. 1 2. 7

<sup>1</sup> Apparent consumption.

## DOMESTIC PRODUCTION

Production of white arsenic in the United States in 1942 declined 12 percent compared with 1941, chiefly because all stocked residues were consumed in 1941. The four producers were the American Smelting & Refining Co., Anaconda Copper Mining Co., Getchell Mine, Inc., and U. S. Smelting, Refining & Mining Co., which derived their output from bag-house and Cottrell dust and speiss. The Getchell company mines gold ores at Red House, Humboldt County, Nev.¹, and in 1942 began to recover the arsenic content by means of a Cottrell precipitator and accessory equipment. Of the domestic white arsenic production in 1942, 89 percent was crude (79–98 percent As<sub>2</sub>O<sub>3</sub>) and 11 percent was refined (99+ percent As<sub>2</sub>O<sub>3</sub>).

<sup>&</sup>lt;sup>1</sup> Van Voorhis, Jr., B. W., Mining Gold-Arsenic and Tungsten Ores at the Getchell Mine: Min. World, vol. 4, No. 12, December 1942, pp. 5-8.

White arsenic produced and sold by producers in the United States, 1938-42

		Crude			Refined			Total	
Year	Produc-	Sa	les	Produc-	Sa	iles	Produc-	Sa	iles
	tion (short tons) <sup>1</sup>	Short tons	Value 2	tion (short tons)	Short tons	Value 2	tion (short tons)	Short tons	Value 2
1938	12, 619 17, 499 18, 241 26, 843 3 25, 658	9, 428 17, 070 16, 688 28, 661 3 27, 981	\$264, 004 343, 000 365, 700 844, 793 1,198,424	4, 066 4, 842 6, 742 5, 638 3, 023	3, 732 5, 369 6, 651 6, 123 3, 057	\$129, 018 152, 500 195, 600 274, 527 161, 942	16, 685 22, 341 24, 983 32, 481 28, 681	13, 160 22, 439 23, 339 34, 784 31, 038	\$393, 022 495, 500 561, 300 1, 119, 320 1, 360, 366

Excludes crude consumed in making refined.

<sup>2</sup> Partly estimated. <sup>3</sup> Includes production of 290 tons of white arsenic and sales of 279 tons contained in compounds made directly from arsenic-bearing ores.

The Anaconda Copper Mining Co. was the sole domestic producer of metallic arsenic in 1942. The Rare Metal Products Co., Belleville, N. J., manufactures arsenic sulfides.

## FOREIGN TRADE 2

Imports of white arsenic—principally from Mexico—increased 59 percent in 1942 compared with 1941. Exports of white arsenic, calcium arsenate, and lead arsenate declined materially.

White arsenic imported for consumption in the United States, 1938-42, by countries

	19	)38	19	939	19	40	19	41	19	42
Country	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
Belgium Canada France Germany	565 689 1, 176 112	\$16, 100 29, 854 30, 843 5, 656	323 471 2, 200 (¹)	\$10, 098 24, 760 50, 224	15 339 1,654	\$1, 152 18, 016 25, 799	862	\$58, 850	1, 449	\$32, 977
Japan Mexico Norway	482 8, 422	17, 199 415, 180	963 8, 124	30, 079 377, 568	224 7, 520 1	10, 307 393, 413 187	193 9, 237	10, 668 528, 488	14, 901	859, 836
Sweden	2, 792 14, 238	93, 197	2, 593 14, 674	69, 304 562, 037	9, 929	4, 156 453, 030	10, 292	598, 006	16, 350	892, 813

<sup>1</sup> Less than 1 ton.

<sup>&</sup>lt;sup>3</sup> Figures on imports and exports (unless otherwise indicated) compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Arsenicals imported into and exported from the United States, 1938-42, by classes, in pounds

Class	1938	1939	1940	1941	1942
Imports for consumption:					
White arsenic	28, 475, 783	29, 347, 810	19, 857, 310	20, 583, 253	32, 700, 351
Metallic arsenic	16, 868	39, 197	13, 228	2, 240	6, 854
Sulfide	241, 602	656, 498	220, 445	11, 025	
Arsenic acid (H <sub>2</sub> AsO <sub>4</sub> )	55	210	,		
Calcium arsenate	400,000	1, 627, 193	432, 785	1, 230, 960	215
Lead arsenate	,	11, 557	,	-,,	
Sheep dip	168, 932	306, 900	341, 556	264, 350	272, 540
Paris green and london purple	103, 556	45, 823	25, 603	12, 000	
Sodium arsenate	11, 881	7, 482	20,000	22,000	
Exports:	,00-	.,			
White arsenic 1	4, 534, 000	6, 356, 933	3, 278, 558	2 3, 231, 536	610, 206
Calcium arsenate	5, 242, 882	6, 731, 103	4, 879, 391	5, 897, 598	3, 941, 722
Lead arsenate	1, 021, 345	1, 712, 583	2, 900, 250	9, 594, 483	592, 029
Paris green (cupric acetoarsenite)	(3)	1, (12, 000	2, 500, 200	224, 976	171, 464

## CONSUMPTION AND USES

Consumption of white arsenic in the United States in 1942, according to the War Production Board, is estimated at 42,411 short tons-73 percent in insecticides, 11 percent in weed killer, 4 percent each in glass and arsenic trichloride, 3 percent in dyes, 2 percent in wood preservative, 0.7 percent in gas purification, 0.4 percent in metallurgy, and 0.3 percent in pharmaceuticals. The results of a special consumer survey for 1941, conducted by the Bureau of Mines, are shown in the following table.

White arsenic consumed in the United States in 1941, by uses

	White arsen	Arsenicals	
Consumed in—	Short tons	Percent of total	manufactured (short tons)
Insecticides: Lead arsenate (normal) Calcium arsenate. Paris green London purple Other insecticides ' Weed killer: Sodium arsenite Poison bait: Sodium arsenite Glass Wood preservative and wall board Dyestuffs. Metal and alloys Miscellaneous '	11, 231 11, 192 1, 523 255 479 7, 123 414 4, 281 1, 366 417 246 1, 915	27.8 27.7 3.8 .6 1.2 17.6 1.0 10.6 3.4 1.0 4.7	36, 65 29, 68 2, 07 67 (1) 2 14, 07- 78
Total white arsenic consumed	40, 442	100.0	

<sup>1</sup> Includes zinc arsenate, basic lead arsenate, copper arsenate, etc.; figures not available for quantity manufactured

Partly estimated.

\*Includes cattle dip, gas purification, arsenic trichloride, pharmaceuticals, paint, etc.

Calcium arsenate is the principal insecticide used to combat the boll-weevil, leaf-worm, and boll-worm infestations in the Cotton Belt; and lead arsenate is employed largely as a spray for apple and pear trees to exterminate codling and gypsy moths and for treating soil in the East to destroy Japanese-beetle grubs. The Department of

As reported to Bureau of Mines by the producers.
 Dealers exported an additional 1,077,244 pounds.
 Not separately classified.
 Figures cover July to December; not separately classified before July 1.

Agriculture anticipates an output of 45,000 tons of calcium arsenate, 31,000 tons of lead arsenate, and 1,250 tons of paris green in 1943. The 1943 outlook was summarized by W. H. Moyer, Insecticides and Fungicides Unit, War Production Board, as follows:

While it has been necessary to curtail sharply many normal uses of arsenic and to require substitution of less scarce materials in many directions, the basic requirements of agriculture for arsenical insecticides should be well provided for during 1943. In some cases, however, farmers will be urged to make greater use of items such as nicotine sulfate and cryolite, which are more plentiful than arsenicals.

Arsenic is an important reagent in glass manufacture, but antimony and cerium <sup>3</sup> are possible substitutes should such use become restricted. The effects of arsenic in glass, described in a recent paper,<sup>4</sup> are summarized as follows:

(1) Blocking agent: Chunks of arsenious oxide thrown into the glass pot sink to the bottom and rapidly volatilize with consequent beneficial stirring action. (2) Fining agent: Arsenic takes oxygen from niter and later liberates it as bubbles which sweep out carbon dioxide, steam, and other gaseous impurities. (3) Oxidizing agent: The oxidizing effect of arsenic helps keep the melt colorless by inhibiting the reduction of ferric oxide to green ferrous oxide. (4) Reducing agent: Arsenic is a reducing agent in respect to manganese and chromium, thus serving to tone down intense manganese colors and to improve chrome greens by removing the yellowish cast of chromates. (5) Color stabilizer: Since both the trioxide and pentoxide are colorless, arsenic is an excellent buffer to absorb variations in oxidizing-reducing conditions and thereby protect changes in the shade of sensitive colors. (6) Opacifying agent: The use of arsenic in making opal (milky-white) glass was widespread in the early days of the industry but is now limited primarily to the white calibration stripes on thermometers and laboratory glassware.

There are a number of disadvantages of using arsenic in glass: (a) Arsenic presents a health hazard to workers. This might be minimized by utilizing calcium or lead arsenate instead of arsenious oxide. (b) Excess additions cause cloudiness, as indicated by its use in opacification. (c) Arsenic is believed to attack glasshouse refractories, but this subject is controversial. (d) Arsenic cannot be used with cerium or neodymium decolorizers because glasses containing such combinations turn brown on exposure to sunlight. (e) Tubing and other glass that is reworked must not contain arsenic, because reheating is apt to

precipitate gray or brown spots of metallic arsenic.

Sodium arsenite is used as a weed killer and as the lethal constituent of poison bait for fighting grasshoppers, Mormon crickets, and white-fringed beetles. Arsenic trichloride is used in the manufacture of lewisite poison gas and arsenic acid for khaki dyes. Arsenic wood-preservative paste and arsenic in other forms are employed to preserve telephone poles, fence posts, cane-fiber insulating board, railroad ties, and mine timbers. White arsenic is utilized in the Thylox method of purifying producer gas. White arsenic and metallic arsenic, its derivative, have limited application in the manufacture of antimonial lead and lead anodes and as a flux or alloying element in copper, brass, white bearing metal, and other alloys. According to the Public Health Service, manufacturers and distributors of arsenical drugs (chiefly the arsphenamines) sold 33 million doses in 1942 for the treatment of syphilis, compared with 18 million in 1941 and 13 million in 1940.

<sup>&</sup>lt;sup>3</sup> Ceramic Industry, Cerium—Logical Arsenic Substitute in Glass Batches: Vol. 40, No. 3, March 1943, pp. 37-38.
<sup>4</sup> Weyl, Woldemar A., The Use of Arsenic in the Glass Industry: Glass Ind., vol. 23, No. 7, July 1942, pp. 263-267, 276.

こうによっているのでは、あるからのできないというと

### STOCKS

Producers' year-end stocks of white arsenic totaled 2,187 short tons in 1942 compared with 4,518 tons in 1941 and 6,944 tons in 1940. The 1942 figure excludes several thousand tons of 79-percent material held by Getchell Mine, Inc. The objective of the Government white arsenic stock pile to be accumulated by the Metals Reserve Co. was set in June 1942 at 6,000 short tons to be delivered by January 1943; this was augmented in July 1942 to provide for an additional 30,000 tons from Peru in 1943–44. The Government stock pile received its first shipment of white arsenic in October 1942 and by the end of the year had on hand 2,693 short tons—1,900 tons from Mexico and 793 tons from domestic sources. Producers' stocks of calcium arsenate and lead arsenate September 30, 1942, totaled 3,030 and 1,679 short tons, respectively, according to the Agricultural Insecticide & Fungicide Association.

## PRICES

The average value of producers' sales of white arsenic was 2.1 cents a pound for crude and 2.7 cents a pound for refined arsenic in 1942

compared with 1.5 and 2.2 cents, respectively, in 1941.

Quotations on arsenic compounds at the end of 1942, according to Oil, Paint and Drug Reporter, were as follows (cents per pound for carlots at Eastern points): White arsenic, 4 cents; calcium arsenate, 7-8 cents; lead arsenate, 11-12 cents; sodium arsenite, 6%-7% cents; sodium arsenate, 8 cents; paris green, 24 cents; and arsenic trisulfide (less than carlots), 30-35 cents. As compared with prices listed at the beginning of the year, these quotations represent a %-cent increase for calcium arsenate and a 1- to 2-cent advance for lead arsenate; otherwise, they are unchanged. A quotation on arsenic metal has not appeared since 1940, when it was nominally 75 cents a pound.

Ceiling prices were placed on arsenic compounds by the Office of Price Administration in the first few months of 1943. The base price of lead arsenate in carlots was set at 11-11½ cents a pound February 8 (Maximum Price Regulation 315). An amendment effective April 6 fixed the base ceiling price of other insecticides as follows (cents per pound in carlots): Calcium arsenate, 7-7½ cents; paris green, 20-25 cents; london purple, 7-8 cents; magnesium arsenate, 15.3-18 cents;

zinc arsenate, 10-11 cents; and zinc arsenite, 11\%-13\% cents.

### WORLD ASPECTS

World production of white arsenic in recent years, insofar as data are available, is shown in the accompanying table.

World production of white arsenic, 1936-42, by countries, in metric tons 1

[Compiled	by	B. B.	Waldbauer]

Country 1	1936	1937	1938	1939	1940	1941	1942
Australia: New South Wales Western Australia Belgium-Luxemburg (exports) Brazil Canada China Chosen France Germany (exports)	2,731 732 619 (2) 230 9,750	2, 087 3, 039 717 630 (2) 	4, 063 2, 706 519 987 (2) (2) (2) (2) 2, 845	(2) 1, 439 3, 332 713 790 (2) (2) (2) (2) (2)	(2) 3,385 (2) 1,088 950 800 (2) (2) (2) (2)	(2) (2) (2) 1, 203 1, 605 (2) (2) (2) (2)	2, 640 (2) (2) (2) 4, 273 (2) (2) (2) (2) (2)
Hungary	85	234 100	(2) (2) 810	(2) (2) (2) (2)	(2) (2) (2) (2) (2)	(2) (2) (2)	(2) (2) (2)
Italy Japan Mexico Portugal Rumania Southern Rhodesia	8,527 150	10, 762 112 6	(2) 8,894 1 3 19	7, 063 426 (²)	9, 268 410 (2)	(2) 12,844 (2) (2) (2) (2) (2) (2) (2)	(2) 18, 520 (2) (2) (2) 4 17
Sweden (sales) 5 United Kingdom United States	8, 647 155	(2) 97 15, 253	(2) 66 15, 136	(2) (2) 20, 267	(2) (2) (2) (2) 22, 664	(2) (2) 29, 466	(2) (2) 26, 019
	55, 700	56, 000	59, 000	63, 000	71, 000	(2)	(2)

<sup>&</sup>lt;sup>1</sup> Arsenic is also believed to be produced in Czechoslovakia, Iran, Peru, Turkey, and U. S. S. R. Production figures are not available for these countries.

Data not available; in 1936 to 1940, inclusive, estimate included in total.

8 Estimated.

Australia.—More than 90 percent of Australia's output of white arsenic in 1942 was produced by the A. V. Leggo Co., Wiluna, Western Australia, from gold ores of the Wiluna and Moonlight mines. source is being exhausted, but about 500 tons of white arsenic could be recovered annually from roaster fumes at the Comet mine, Marble Bar, Western Australia.

Canada. - Production of arsenic in Canada in 1942 was several times that in 1941. White arsenic is produced by Beattie Gold Mines, Ltd., Duparquet, Quebec; O'Brien Gold Mines, Ltd., Cadillac Township, Quebec; and Deloro Smelting & Refining Co., Ltd., Deloro, The Deloro company has a contract with the United Kingdom to supply refined white arsenic at 7% cents a pound for the first 2,000 tons and 6% cents for additional quantities. Wampum Gold Mines, Ltd., a company controlling the property of Douglas Lake Mines, Ltd., in Saskatchewan about 3 miles southwest of the Flin Flon mine, is developing an arsenopyrite body containing more than 10,000 tons of ore averaging 22 percent As and 0.5 ounce of gold per ton and 40,000 tons of lower-grade ore. The company has a contract to deliver 2,500 short tons of white arsenic within 2 years to the Metals Reserve Co., United States Government stock-piling agency.6 The possibility of recovering 350 tons of white arsenic monthly from the Hard Rock and MacLead-Cockshutt gold mines in the Little Long Lac district of Ontario was considered seriously in 1942,7 but the proposition later was abandoned.8 Three mines in British Columbia-Hedley Mascot Gold Mines, Ltd., Kelowna Exploration Co.,

<sup>August to December, inclusive.
Arsenic content of ores mined was as follows—1936: 23,312 tons; 1937: 20,954 tons; 1938: 21,480 tons; data</sup> not available for later years.

Northern Miner, vol. 28, No. 49, February 25, 1943, p. 4.
 Canadian Mining Journal, vol. 63, No. 11, November 1942, p. 742,
 Northern Miner, vol. 28, No. 35, November 19, 1942, p. 5.
 Northern Miner, vol. 28, No. 50, March 4, 1943, p. 1.

ARSENIC 761

Ltd., and Bralorne Mines, Ltd.—ship arsenic-bearing concentrates to the Tacoma (Wash.) smelter of the American Smelting & Refining Co. The Canadian Pacific Railway uses antimonial lead babbit containing 0.75–1.25 percent As and thus conserves appreciable quantities of tin.<sup>9</sup>

Ecuador.—A deposit containing 5-10 percent realgar has been

located at Macas, Province of Cotopaxi, Ecuador.

Mexico.—Both production and exports of white arsenic in 1942 increased 44 percent over 1941. Exports totaled 18,065 metric tons—

18,040 tons to the United States and 25 tons to Argentina.


Peru.—During the first half of 1942 the Oroya smelter of the Cerro de Pasco Copper Corporation produced 76 metric tons of lead-antimony bars containing 1.9 percent As. The corporation has a contract with the Metals Reserve Co., United States Government stockpiling agency, to deliver 10,000 tons of refined white arsenic during 1943.

Sweden.—Arsenic is recovered from Boliden ores in such quantities as to make Sweden, the world's largest producer. White arsenic now stored in concrete silos in that country is believed to exceed 300,000 tons. It is reported that Great Britain has obtained an agreement from Sweden not to ship any of this material to Germany during the present war.

United Kingdom.—Refined white arsenic in 20-ton lots was quoted at £40 per long ton and metallic arsenic at £375 per long ton at the

end of 1942, according to Metal Bulletin.

<sup>9</sup> Sylvester, I. I., Alternative Babbitts: Eng. Jour., vol. 25, No. 9, September 1942, pp. 502-504.



# **BISMUTH**

By Allan F. Matthews

### SUMMARY OUTLINE

	Page		Page
General statement	763	Stocks	765
Production	762	Prices	765
Production		World aspects	765
Foreign trade		World aspects	
Congression and uses	764		

## GENERAL STATEMENT

Bismuth production in the United States in 1942 increased one-fourth over 1941, and consumption doubled. As there were no imports of metal to bridge the gap, stocks declined. Allocation control was instituted by the War Production Board over metallic bismuth February 1, 1943 (Order M-276), and over bismuth chemicals April 1, 1943 (Order M-295). The tariff on metallic bismuth was reduced 50 percent July 29, 1942.

## PRODUCTION

Bismuth metal production in the United States reached an all-time high in 1942 and exceeded by one-fourth the record set in 1941. The Bureau of Mines is not at liberty to publish data showing domestic production of bismuth. Three primary producers recover byproduct bismuth principally from domestic and imported lead and copper ores and from Mexican bismuth-lead bullion bars. The American Smelting & Refining Co. produces bismuth-lead alloys at its Selby (Calif.), Perth Amboy (N. J.), and Monterrey (Mexico) plants for refinement at Omaha, Nebr. From Montana copper and Utah lead ores the Anaconda Copper Mining Co. at Tooele, Utah, produces bismuth-lead bullion, which is refined by its subsidiary, International Smelting & Refining Co., East Chicago, Ind. The United States Smelting, Refining & Mining Co. ships bismuth-lead bullion from Midvale, Utah, for refinement at East Chicago, Ind., by its subsidiary, the U. S. S. Lead Refinery, Inc. The principal importer-consumer is the Cerro de Pasco Copper Corporation, New York, which produces large quantities of bismuth in Peru.

As a conservation measure, the use of metallic magnesium in debismuthizing lead was prohibited by the War Production Board November 14, 1941 (Order M-2b). The situation was allayed somewhat in 1942 by the allocation of magnesium turnings and sawings for this purpose, and in June 1943 it appeared that pure magnesium metal

would again be available for debismuthizing lead.

## FOREIGN TRADE 1

Imports.—There were no "imports for consumption" of metallic bismuth in 1942, but "general imports" totaled 222,684 pounds—all of which apparently was either in bonded warehouses at the end of the year or had been reexported. Except for 570 pounds from Canada in 1938, all entries of metallic bismuth in 1938—42 were from Peru. As a result of the Reciprocal Trade Agreement with Peru, effective July 29, 1942, the tariff duty on metallic bismuth imports from "most-favored nations" has been reduced to 3½ percent ad valorem compared with the former level of 7½ percent set by the Smoot-Hawley Tariff Act of 1930.

Bismuth and "compounds, mixtures, and salts of bismuth" imported for consumption in the United States, 1938-42

	Year		Bisn	nuth	Compounds, mixtures, and salts of bismuth		
				Pounds	Value	Pounds	Value
1938 1939			 	92, 298 182, 832	\$74, 583 154, 339	2, 004 297	\$3, 38
1940 1941 1942			 	123, 880 223, 477	118, 260 223, 463	4 41	649 31 744
1012			 			7	2:

Exports.—Bismuth exports in 1942 and in the latter part of 1941 are shown in the accompanying table. Earlier data are not available.

Bismuth exported from the United States, 1941-42

Bismuth commodity	1941 (Sep Decem		1942		
	Pounds	Value	Pounds	Value	
Matte	1 4, 708 1 433, 652 31, 818 20, 732 11, 269 82, 990 163 111	1 \$3, 250 1 441, 721 41, 633 34, 143 17, 772 126, 667 677 356	11, 495 14, 827 146, 769 70, 356 19, 012 1, 002 450 317 30 2 25, 129	\$6, 387 10, 254 98, 812 91, 674 28, 748 1, 965 1, 701 832 45 4 36, 651	

<sup>1</sup> Figures for matte and for metal and alloys cover July to December, inclusive; earlier data not available.

## CONSUMPTION AND USES

Consumption of bismuth in 1942 was double that of 1941 and quadruple that of 1940. Bismuth metal shipped by producers and importers is estimated to have comprised 45 percent for use in pharmaceuticals and other compounds; 31 percent in solders and bearings; 15 percent in spotting fixtures, die setting, anchoring machine-tool bushings, and tube bending; and 9 percent in miscellaneous applications. Corresponding estimates for these four categories in 1941 are

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

60, 10, 15, and 15 percent, respectively. The data for 1942 are adjusted to exclude a significant quantity of metal stocked for use in 1943 but shipped in 1942 with the intention of using it in solder for armor-piercing shells, a requirement eliminated by the decision to employ crimping as an alternative of soldering. The year 1942 was the first in which the metallurgical applications of bismuth were

quantitatively more important than the pharmaceutical.

Bismuth compounds are used in treating indigestion, venereal diseases, and wounds; in controlling blue mold on tobacco; and as a constituent of cosmetic powders. Alloys of bismuth are important because of their low melting point and because their volume either expands or is unchanged upon solidification from melts. Bismuth is a constituent of certain tin-lead solders; a recent series designed to conserve tin contains 75 to 82.5 percent Pb, 10 to 20 percent Sn, 3 to 5 percent Bi, 1.5 to 2 percent Ag, and 0.5 to 1 percent Sb. Low-melting alloys of bismuth (43-55 percent) with lead, tin, and cadmium are used in spotting fixtures, die setting, anchoring machine-tool bushings, and tube bending. Similar alloys, some with melting points as low as 117° F., are used in sprinkler apparatus, fire-detector systems, and valve seats for high-pressure gas containers. Additions of 0.1 to 1.5 percent bismuth to stainless steel, copper, and aluminum alloys improve machinability.

STOCKS

Inventories of bismuth held in the United States by the three domestic producers and the principal importer-consumer dropped 51 percent in 1942. In part the trend represented transfers from producer to Government stocks; thus, the over-all change in in-

ventories at this level was a 33-percent decline.

Government-owned Metals Reserve Co. began stock-piling bismuth in July 1942 and by the end of the year had on hand 352,701 pounds—all refined in the United States but including 211,660 pounds imported from Mexico in bismuth-lead bullion. The Government stock pile comprised 592,586 pounds in mid-May 1943. The recommended stock-pile objective for bismuth was set in May 1942 at 500,000 pounds, in October at 1,500,000 pounds, and in November at 2,000,000 pounds.

PRICES

Bismuth metal continued throughout 1942 to be quoted at \$1.25 a pound, ton lots, according to E&MJ Metal and Mineral Markets. Prices of bismuth compounds (in fiber drums)—likewise unchanged—were listed by Oil, Paint and Drug Reporter as follows, per pound: Subnitrate, \$1.20; subcarbonate, \$1.50; subgallate, \$1.40; subsalicylate, \$2.50; subiodide, \$4.13; and trioxide, \$3.65. Despite the steady base price, the quotation on subnitrate, subcarbonate, and subgallate in small lots (5-pound bottles) declined 11 to 15 percent in 1942.

WORLD ASPECTS

World production of bismuth approximated 1,700,000 kilograms (3,700,000 pounds) in 1942 compared with 1,400,000 kilograms (3,000,000 pounds) in 1941. It appears that the United Nations control about 88 percent of the new supply. The principal producing countries are the United States, Peru, Canada, and Mexico.

# World production of bismuth, 1937-42, by countries, in kilograms' [Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
Argentina Australia (in ore) <sup>4</sup> Bolivia (in ore and bullion exported) <sup>8</sup>	<sup>2</sup> 3, 560 ( <sup>3</sup> ) 30, 818	4, 600 17, 194	\$ 2,860 2,200 12,653	4, 880 2, 800 18, 700	(3) 2, 200 22, 604	( <sup>3</sup> ) 4, 800 8, 896
Canada: Metal In bullion Mexico (in impure bars) Norway (in ore)	2, 590 141, 684 360	4, 316 185, 797 470	185, 722 163, 683 (³)	18, 479 8, 069 185, 433 (3)	3, 401 97, 971 (3)	156, 027 1, 043 128, 041 (3)
Peru: Metal In lead-bismuth alloy Spain (in ore)	67, 002 18, 415	201, 961 13, 178	402, 027 52, 430	387, 479 56, 314 41, 830	276, 907 178, 138 (3)	6 338, 000 6 12, 000 (3)
Union of South Africa (in ore) United States	( <sup>7</sup> )	2, 636	1, <b>37</b> 9	(3)	(3)	(3)
기 등을 보지 말해 들어 들어가면 되었습니다. 이 크리나 그 등이 모든데 이 등장에 보고 이 모든데	700,000	1,000,000	1, 300, 000	1, 400, 000	1, 400, 000	1,700,000

<sup>&</sup>lt;sup>1</sup> Bismuth is also believed to be produced in Brazil, Burma, China, France, Germany, Japan, Rumania, Sweden, Uganda, U. S. S. R., United Kingdom, and Yugoslavia. Production figures are not available for these countries, but estimates by author are included in total.

Mexico.—Impure bismuth bars containing lead and small quantities of gold and silver are recovered as a byproduct of lead by the American Smelting & Refining Co., Monterrey, Nuevo Leon, Mexico, and are exported to the company Omaha (Nebr.) plant for refining. The lead operations at Monterrey of Campañia Metalurgica de Peñoles, S. A., subsidiary of the American Metal Co., Ltd., yield an unrefined lead-bismuth alloy which is treated on toll basis by the American Smelting & Refining Co.

Peru.—In 1942 Peru exported 355,728 kilograms of refined bismuth bars, containing 325,737 kilograms of bismuth, and 38,744 kilograms of bismuth-lead bars, containing 20,244 kilograms of bismuth. Of these exports, 73 percent went to the United Kingdom, 26 percent to the United States, and 1 percent to Chile. Bismuth ores are mined in the Department of Junin, principally at the San Gregorio mine and secondarily at the Colquijirca mine, and are smelted at

Oroya by the Cerro de Pasco Copper Corporation.

Spain.—Bismuth ore produced in Spain, all in the Province of Córdoba, had a content of 42 metric tons of bismuth in 1940 compared with 95 in 1935, 180 in 1934, and 77 in 1933; there was no production in 1936-39 as a consequence of civil war. Some of the ore is consumed domestically, and the resultant output of bismuth metal was 11 metric tons in 1940 compared with none in 1936-39,

44 in 1935, 46 in 1934, and 26 in 1933.

United Kingdom.—London bismuth quotations were unchanged throughout 1942, according to Metal Bulletin. Bismuth ore, 30 to 35 percent, was listed at £110 to £125 a long ton, high-grade metal at 6s. 3d. a pound, and matrix alloy at 4s. 1d. a pound. Bismuth compounds and preparations were placed under export license

control November 16, 1942.2

 <sup>2</sup> Data not available. Estimate included in total.
 4 Partly estimated. Excludes content of some bismuth-tungsten concentrates.
 5 Excludes bismuth content of tin concentrates exported.

<sup>Preliminary figure.
Production included in total; Bureau of Mines not at liberty to publish figure.</sup> 

<sup>2</sup> Metal Bulletin (London), No. 2741, November 6, 1942, p. 5.

# **MAGNESIUM**

By John H. Weitz and M. E. Trought

### SUMMARY OUTLINE

	Page		Page
Summary	 767	Prices	778
Salient statistics	 767	Foreign trade	
Production	 768	Technologic developments	776
	 773	World production	777
War measures	 77.5		

### SUMMARY

Spurred onward by the unprecedented demand for airplanes and incendiary bombs, magnesium in the short space of a year has increased greatly in importance among the nonferrous metals. Production in 1942 exceeded the combined output of the industry from its inception in 1915 through 1941. On the basis of military requirements, the War Production Board announced the second expansion program early in 1942, increasing annual capacity to 725,000,000 pounds; this goal was cut back to 610,000,000 pounds and finally to 586,000,000 pounds later in 1942. Production of primary magnesium in 1942 totaled 97,925,684 pounds—200 percent more than in 1941 (32,589,052 pounds) and 682 percent greater than in 1940 (12,521,726 pounds). Magnesium output, having reached an annual rate of 218,800,000 pounds in December 1942, is expected to total nearly 375,000,000 pounds during 1943.

## Salient statistics of the magnesium industry in the United States, 1940-42

	1940	1941	1942
Production of primary magnesium pounds Quoted price per pound 1 cents Exports pounds World production (estimated) short tons		32, 589, 052 22. 5 2 3, 098,424 85, 500	97, 925, 684 22, 5 2 8, 090, 449 154, 400

Lowest nominal price (New York) for primary metal ingot 99.8 percent pure, carlots.
 Magnesium metal in primary form.

Dow Chemical Co. and Dow Magnesium Corporation produced the largest proportion of the domestic output and began operating a third plant during 1942. The carbothermic reduction plant of Permanente Metals Corporation continued production throughout the year, and most of the technical difficulties appear to have been solved. Permanente began production from a new ferrosilicon plant at Manteca, Calif., during the year, and seven new companies in the field began operations in 1942, contributing substantially to the year's output. These included Diamond Magnesium Co. at Painesville, Ohio; Basic Magnesium, Inc., at Las Vegas, Nev.; Ford Motor Co.

at Dearborn, Mich.; International Minerals & Chemicals Corporation at Austin, Tex.; Magnesium Reduction Co. at Luckey, Ohio; Mathieson Alkali Works, Inc., at Lake Charles, La.; and New England Lime

Co. at Canaan, Conn.

Domestic consumption of primary and secondary magnesium in 1942 totaled 84,525,700 pounds compared with 29,346,600 pounds in As in 1941, demand for the metal continued greater than the available supply, and magnesium topped the list of critical metals issued periodically by the War Production Board. The situation had eased somewhat by mid-1943, but virtually all the metal was still being allocated to direct military uses and to Lend-Lease account and will probably continue to be so allocated for the duration of the war. Of the primary magnesium shipped or used in 1942, approximately 58 percent went into the production of magnesium-base alloys, virtually all for structural products; 12 percent into other alloys, chiefly aluminum; 17 percent into magnesium products, chiefly nonstructural; 11 percent for export account; and 2 percent into other uses. primary magnesium was imported, but more than 8,000,000 pounds were exported in 1942. The second major price reduction in less than 2 years was made when the Dow Chemical Co. reduced its price on 99.8-percent magnesium ingot, carlots, from 22.5 cents to 20.5 cents a pound on January 1, 1943. The Office of Price Administration ordered that, effective February 1, all ingot sales except those to Metals Reserve Co. would be regulated by a ceiling price of 20.5 cents a pound.

World magnesium output reached a new peak in 1942, and estimates based on meager statistical data indicate that Germany remained the largest producer. Axis and Axis-dominated nations produced an estimated 52 percent of the world output in 1942, but it is anticipated that the United Nations will greatly exceed Axis production

in 1943.

### PRODUCTION

Primary magnesium.—Domestic production of primary magnesium in 1942 totaled 97,925,684 pounds, a 200-percent advance over the 32,589,052-pound output of 1941. Primary magnesium shipped or used (sales) totaled 94,840,771 pounds, or 205 percent more than in 1941 (31,056,947). Although the Dow Chemical Co. and the Dow Magnesium Corporation produced most of the output, the Permanente Metals Corporation, New England Lime Co., Mathieson Alkali Works, Inc., Ford Motor Co., Basic Magnesium, Inc., Diamond Magnesium Co., Magnesium Reduction Co., and International Minerals & Chemicals Corporation contributed a substantial share.

United States production is expected to reach nearly 375,000,000 pounds in 1943 and 530,000,000 pounds in 1944. By June 1944 it is estimated that domestic facilities will be producing at their rated ultimate capacity of 586,000,000 pounds. In early 1941 peak estimates of military requirements amounted to only 72,000,000 pounds, but by June 1941 requirements had increased to an estimated 411,-000,000 pounds, according to the Office of Production Management; of this total, 153,000,000 pounds was for so-called "contingency requirements." The first expansion, increasing capacity to 400,000,-000 pounds annually, to take care of revised requirement schedules, was announced June 13, 1941.

The state of the s

At the end of 1941, military requirements had risen to the point where peak possible consumption was stated as 670,000,000 pounds, including 470,000,000 pounds for Chemical Warfare Service and for bombs to be exported (now estimated at only 170,000,000 pounds). In February 1942 the War Production Board announced its second expansion program designed to increase total annual primary metal capacity to 725,000,000 pounds. Requirements were again revised—this time downward to approximately 600,000,000 pounds—and the construction program was cut back to 610,000,000 pounds. The goal was again cut back to 586,000,000 pounds, and this capacity, plus about 32,000,000 pounds of secondary metal, is expected to supply enough magnesium for all requirements planned at present. About 90 percent of all the domestic magnesium-producing capacity will be Government-owned when the expansion programs are completed.

Dow Chemical Co., the largest domestic producer during 1942, produced metal from an underground brine containing 3.2 percent MgCl<sub>2</sub> at its 18,000,000-pound Midland (Mich.) plant and from sea water at its 36,000,000-pound Freeport (Tex.) plant. At Midland the bromine and the sodium and calcium salts are removed from the brine by evaporation, filtration, and fractional crystallization, and some chlorine is added during the process. The purified magnesium chloride solution remaining is concentrated further by crystallization to give MgCl<sub>2</sub>·6H<sub>2</sub>O (hexahydrate). The hexahydrate is dried to give a nearly anhydrous magnesium chloride (MgCl<sub>2</sub>·H<sub>2</sub>O) and, with some added sodium chloride, is then electrolyzed in the fused state in rectangular cast-steel cells. At Freeport, Tex.,1 vast quantities of sea water containing only about 0.12 percent magnesium (0.48 percent MgCl<sub>2</sub>) are treated with hydrated oystershell lime. Magnesium hydroxide is precipitated and then reacted with hydrochloric acid produced from gases given off by the electrolytic cells. The resulting solution is evaporated to give crystals of the hexahydrate, which are dried and treated as at Midland.

Dow Magnesium Corporation was formed to construct and operate two 72,000,000-pound magnesium plants at Velasco, Tex., and Marysville, Mich., both using the standard Dow process. The Velasco plant uses the same process as the Freeport (Tex.) plant of the Dow Chemical Co., and is only 7 miles away; it began producing magnesium from sea water in June 1942. On April 8, 1943, the mammoth Marysville plant began to produce magnesium.<sup>2</sup> Ultimately this plant will use magnesium chloride shipped from Ludington, Mich., where 10percent magnesium chloride brines were tapped and developed in 1941. The Ludington feed plant was not completed and could not supply the Marysville reduction plant for the first 2 months of operation; during this period magnesium chloride was shipped from Texas in hopperbottomed cement cars. Although the process used to convert magnesium chloride to metal at Marysville is essentially the same as at Midland, the new plant embodies many notable advances in chemical Because of the shortage of copper, silver bus bars carry engineering. electric current in the Marysville plant. The silver—2,000,000 pounds valued at \$20,000,000—was loaned to the Defense Plant Corporation by the Government and will be returned when the bars can be replaced by copper.

<sup>1</sup> Wilson, P. D., Enlarging Magnesium Output: Met. Ind., vol. 16, No. 13, September 25, 1942, pp. 203-204.

2 Van Antwerpen, F. J., The First Magnesium Poured at Dow's Sixth Plant: Chem. and Eng. News, vol. 21, No. 8, April 25, 1943, pp. 546-547.

The Mathieson Alkali Works, Inc., which, up to June 6, 1943, was producing only small amounts of metal from a pilot plant at Lake Charles, La., began production from the first unit of its 54,000,000-pound plant on that date. Mathieson has developed a special electrolytic cell jointly with the Consolidated Mining & Smelting Co. (Trail, B. C.) known as a Trail-Mathieson cell.<sup>3</sup> Advantages claimed for this cell over the standard Dow cell are that concentrated chlorine gas is produced instead of hydrochloric acid gas and that a lower consumption of electric current per pound of metal is indicated. The raw material used is dolomite, Mg,Ca(CO<sub>3</sub>)<sub>2</sub>, which is calcined and treated with waste calcium chloride liquor from the company Solvay process. Hot waste carbon dioxide gas from the calcining kilns is passed through the solution; calcium carbonate is precipitated and filtered off. The magnesium chloride brine is concentrated, evaporated to hexahydrate, and dried to a nearly anhydrous form for electrolysis.

Production began at the 36,000,000-pound plant operated by the Diamond Magnesium Co. at Painesville, Ohio, late in September 1942. Like Mathieson Alkali, Diamond treats dolomitic lime with the chloride waste liquors from its Solvay ammonia-soda process to produce magnesium hydroxide and calcium chloride. The slurry is carbonated by kiln gases, and calcium carbonate is precipitated. The remaining solution is concentrated and crystallized, and the crystals are dried to produce a nearly anhyrous magnesium chloride cell feed. In addition to the recovery of magnesium chloride by using waste chloride liquors, Diamond treats some calcined dolomite directly with hydrochloric acid from the cell gases. The regular Dow-type

cell is used in electrolytic decomposition of the chloride.

Magnesium was produced by International Minerals & Chemicals Corporation at its 24,000,000-pound plant at Austin, Tex., starting in November 1942, from purchased magnesium chloride cell feed. Union Potash & Chemical Co. at Carlsbad, N. Mex., a subsidiary of International, began supplying the Austin plant with magnesium chloride cell feed derived as a byproduct from its potash operations in the early summer of 1943. Part of the cell feed for the Austin plant is being obtained from hydrated dolomite quarried in Burnet County, Tex., which is carbonated with kiln gases and treated with byproduct

hydrochloric acid from the Dow-type electrolytic cells.

On August 31, 1942, Basic Magnesium, Inc., began production from its huge 112,000,000-pound plant at Las Vegas, Nev. The plant, which uses the M. E. L. process developed by I. G. Farbenindustrie, A. G., in Germany and later used by Magnesium Elektron, Ltd., at Clifton Junction, England, is the largest magnesium plant in the world and is patterned after the Magnesium Elektron (Ltd.) plant in England. Production was slow in getting under way, owing to concentrating difficulties at the magnesite mine in Gabbs Valley, Nev., and to other factors. During the summer and fall of 1942 charges of company mismanagement were made by Senator Bunker of Nevada and others, and in late October it was announced that the 52%-percent interest in the company owned by Basic Refractories, Inc., of Cleveland, Ohio, had been purchased by the Anaconda Copper Mining Co. for a reported \$75,000. Production during April 1943 had risen to about 63 percent of rated capacity. Raw magnesite

<sup>&</sup>lt;sup>2</sup> Center, A. A., Electrometallurgy: Eng. and Min. Jour., vol. 144, No. 2, February 1943, pp. 106-108, 151.

and magnesium oxide sinter are ground and briquetted with coke and British Columbia peat moss. To produce a completely anhydrous magnesium chloride, the briquets are roasted and treated with chlorine gas obtained partly from the cells and partly from the electrolysis of sodium chloride. The principal difference between the electrolysis in the M. E. L. process and in the Dow process is that the latter uses a monohydrated magnesium chloride cell feed whereas the former uses a

completely anhydrous feed.

Permanente Metals Corporation operated two plants using different processes during 1942. One plant which began operations late in 1941 uses the so-called Hansgirg process, a carbothermal reduction method, but was a great disappointment throughout most of 1942. Production lagged far behind schedule, and reports of accidents and explosions were numerous; however, in the latter part of 1942 and during the first half of 1943 production has increased markedly, and there are indications that most of the technical difficulties have been overcome. In the Hansgirg process, coke and caustic calcined magnesia are mixed and heated in a 3-phase 8,000-kv.-a. electric-arc furnace to about 2,100° C. The coke reduces the magnesia, and the magnesium becomes vaporized. Shock cooling by natural gas at 200° C. and collection of the dust by Cottrell precipitators yields a finely divided magnesium powder mixed with carbon, magnesia, and other impurities, which is collected as a doughy mixture in oil. The mixture is redistilled, and the magnesium is removed as high-purity crystals from the top of the distilling furnace. Sea-water magnesia for the process was obtained from the Westvaco Chlorine Products Co. until late in 1942, when Permanente began operating its own sea-water magnesia plant at Moss Landing, Calif. The other metal plant operated by Permanente is at Manteca, Calif., and uses the new ferrosilicon process developed by Dr. L. M. Pidgeon of Canada. Production at this plant began in August 1942.

Including the Permanente Metals Corporation plant at Manteca, six companies are operating plants using the ferrosilicon process. The-other five are: Ford Motor Co., Dearborn, Mich.; Electro Metallurgical Co., Spokane, Wash.; Magnesium Reduction Co. (National Lead Co.), Luckey, Ohio; Amco Magnesium Co. (American Metals Co.), Wingdale, N. Y.; and New England Lime Co., Canaan, Conn. Research on this process was pioneered by Dr. L. M. Pidgeon of the Canadian Research Council, the Ford Motor Co. at Dearborn, Mich., and the Electro Metallurgical Co. at Niagara Falls, N. Y. Dolomite, a double carbonate of calcium and magnesium occurring in virtually limitless quantities in the United States, is the magnesium-bearing raw material used. Dead-burned dolomite and ferrosilicon (75-percent grade) are briquetted and charged into a horizontal or vertical nichrome-steel retort equipped with a condenser unit and heated at, about 1,150° C. under a high vacuum. The magnesium oxide in the calcined dolomite is reduced by the ferrosilicon, and the metal is vaporized and collected at the cooled end of the retort. After most of the magnesium has been driven off the charge, the retort is opened, and a ring of high-purity magnesium crystals is

<sup>4</sup> Stedman, G. E., Ford Makes Magnesium: Chem. and Met. Eng., vol. 49, No. 9, September 1942, pp. 134-137. Ramsay, R. H., Dominion Magnesium—Trail Blazer: Eng. & Min. Jour., vol. 144, No. 5, May 1943, pp. 56-61.

4 Weitz, John H., High-Grade Dolomite Deposits in the United States: Bureau of Mines Inf. Circ. 7226, 1942, 86 pp.

removed. The residue in the retort—largely dicalcium silicate, calcium oxide, and some magnesium oxide and ferrosilicon—is removed and disposed of, and the cycle is begun again with a fresh charge of briquets. Approximately 12 pounds of dolomite and 1 pound of ferrosilicon are required to produce 1 pound of magnesium metal. The process was adopted because it requires less electric power than the electrolytic processes, it employs dolomite (a cheap and abundant raw material), and the plants utilizing it require a minimum of time for construction.

The Ford Motor Co. plant, which began operations in May 1942, experienced trouble with collapse of its retorts owing to internal and external corrosion and the shock of heating. Research showed that if the retorts could be embedded in a bath of molten silicate glass, the possibility of collapse would be lessened and a mild low-carbon steel could be used. Original plans were changed to include 24 Toledo furnaces and 12 silicate furnaces at the Dearborn plant.

Vertical internally heated retorts are used at the Electro Metallurgical Co. plant at Spokane, Wash., which began operation on May 26, 1943. This company is building its own 48,000,000-pound ferrosilicon plant, which is already in partial operation at Spokane.

In September 1942 the plant of the New England Lime Co. at Canaan, Conn., began producing magnesium. After several months of operation, difficulties were experienced with the collapse of retorts; but the company's experiments showed that the life of these retorts could be prolonged by the simple expedient of blowing them up again with compressed air.

Magnesium Reduction Co. at Luckey, Ohio, began operations in December 1942, using high-grade Ohio dolomite, and Amco Magnesium Co., Wingdale, N. Y., began production in April 1943 using purchased lime. Local dolomite will be employed by Amco as soon as the

calcining kilns are completed.

Explosions and fires destroyed the plants of Magnesium Products, Inc., Los Angeles, Calif. (aircraft castings), and National Magnesium Corporation, Newark, N. J., during 1942. In March 1943 the plant of the Pacific Coast Chemical Co. at Aberdeen, Wash., was destroyed

by a series of explosions and a large fire.

Among old and new companies that expanded or began to fabricate magnesium in 1942 and the first half of 1943 through the Defense Plant Corporation were: American Radiator & Sanitary Corporation, Elyria, Ohio, and Louisville, Ky.—castings for aircraft engines and wheels (3,600,000 pounds at each plant annually); Chevrolet Motor Division, General Motors Corporation, Saginaw, Mich.—castings (4,800,000 pounds annually); Bendix Aviation Corporation, Bendix, N. J.—castings (1,920,000 pounds annually); Deere & Co., East Moline, Ill.—castings (2,400,000 pounds annually); Dow Chemical Co., Bay City, Mich.—sand castings (1,680,000 pounds annually), and Midland, Mich.—extrusions (2,640,000 pounds annually); Ebaloy Foundries, Inc., Rockford, Ill.—castings (1,800,000 pounds annually); Ferro Enamel Corporation, Bedford, Ohio—powder (200,000 pounds monthly); Hills-McCanna Co., Chicago, Ill.—sand castings (6,000,000 pounds annually); Howard Foundry Co., Chicago, Ill.—sand castings (6,000,000 pounds annually); Humphreys Mfg. Co., Mansfield, Ohio—castings (2,400,000 pounds annually); Marshall Stove Co., Lewisburg, Tenn.—castings (4,200,000 pounds annually); Maryland Sani-

The state of the s

The same of the sa

tary Mfg. Co., Baltimore, Md.—castings (6,000,000 pounds annually): Michigan Light Alloys, Grand Rapids, Mich.—castings (4,200,000 pounds annually); Revere Copper & Brass, Inc., Baltimore, Md.—sheet (6,000,000 pounds annually), and Rome, N. Y.— forgings; Springfield Bronze & Aluminum Co., Springfield, Mass.—castings (3,600,000 pounds annually); U. S. Radiator Corporation, Geneva. N. Y.—castings (3,600,000 pounds annually); and Wellman Bronze & Aluminum Co., Cleveland, Ohio—castings (3,600,000 pounds annually).

Secondary magnesium.—Recovery of secondary magnesium totaled 6,238 short tons (including secondary magnesium incorporated in primary magnesium ingot) in 1942 and required the consumption of 7,317 tons of magnesium scrap, which was almost entirely new scrap. Of the quantity of magnesium recovered, 6,045 tons were as ingot, and 93 tons went into castings, 46 into aluminum alloys, 2 into lead alloys, 1 into zinc alloys, and 51 into chemical reagents. Additional information on secondary magnesium will be found in the chapter on Secondary Metals—Nonferrous.

## CONSUMPTION

Magnesium remained under strict priority control during 1942 to insure that virtually all of the metal was channeled into military uses for the production of airplanes and incendiary bombs. Apparent consumption totaled 86,750,322 pounds—an increase of 210 percent over 1941. Of the primary magnesium shipped or used in 1942 (94,840,771 pounds), approximately 58 percent was used in the production of magnesium-base alloys, virtually all for structural products; 12 percent in other alloys, chiefly aluminum; 17 percent in magnesium products, chiefly nonstructural; 11 percent for export account; and 2 percent in other uses.

Actual consumption of magnesium (from primary and secondary sources) totaled 84,525,700 pounds. Of this, 75 percent was used

Production, sales, exports, and apparent consumption of primary magnesium in the Únited States, 1940–42, in pounds

Year	Production	Sales	Exports	Apparent consumption 1					
1940	12, 521, 726 32, 589, 052 97, 925, 684	12, 823, 633 31, 056, 947 94, 840, 771	<sup>2</sup> 1, 668, 765 3, 098, 424 8, 090, 449	11, 154, 868 27, 958, 523 86, 750, 322					

<sup>&</sup>lt;sup>1</sup> Does not consider fluctuations in consumers' stocks and metal derived from scrap. Withdrawals from producers' stocks totaled 301,907 pounds in 1940; additions to producers' stocks totaled 1,447,615 pounds in 1941 and 3,084,913 in 1942.

2 Of the 1,718,444 pounds of metal exported, 49,679 pounds consisted of magnesium alloy.

Actual domestic consumption of primary and secondary magnesium (magnesium content), 1941-42, by uses, in pounds

Use 1941		1942	Use	1941	1942
Structural products <sup>1</sup>	21, 951, 900 6, 762, 200	63, 519, 400 14, 317, 200	ChemicalsOther	27, 600 32, 300	22, 900 23, 300
Other alloys Scavenger and deoxidizer_ Pyrotechnics	59, 000 130, 400 383, 200	2 431, 100 211, 800 6, 000, 000	Total	29, 346, 600	84, 525, 700

<sup>1</sup> Castings, sheet, extruded shapes, forgings, etc.
2 Includes 396,100 pounds of magnesium contained in 50-50 aluminum-magnesium alloy.

in the manufacture of magnesium-base alloy structural products, 17 percent in aluminum alloys, 7 percent in pyrotechnics, and 1 percent in other uses.

Magnesium-base alloy structural products manufactured and sold or used in the United States increased 233 percent over 1941. The manufacture of nonstructural products sold or used increased 658 percent. Of the structural products sold or used, sand castings comprised 70 percent, permanent mold castings 24 percent, die castings 3 percent, sheet 2 percent, and other structural products 1 percent. Of the nonstructural products, powder comprised 59 percent, stick 40 percent, and shavings, turnings, wire, ribbon, and other products 1 percent. The value of sand castings manufactured in 1942 averaged \$2.22 a pound, permanent mold castings \$0.83, die castings \$1.87, and all castings \$1.87 a pound (compared with \$2.03 in 1941).

Magnesium products (other than ingot) manufactured in the United States and sold or used by the companies manufacturing the products, 1940-42

Product	19	<b>)40</b>	19	941	1942	
Froduct	Pounds	Value	Pounds	Value	Pounds	Value
Structural products: Castings:						
Sand Permanent mold Die	3, 973, 757 699, 212	\$7, 345, 050	11,944,618	\$24,669,146	{32, 024, 393 10, 800, 023	\$71, 176, 648 9, 015, 586
SheetStructural shapes, rods,	322, 664	653, 289 246, 476	768, 162 431, 306	1, 155, 048 309, 749	1, 346, 077 876, 577	2, 518, 697 684, 122
tubing (extrusions) Forgings Other structural	410, 912 25, 938 43, 047	349, 123 34, 602 134, 251	451, 394 25, 734 54, 119	313, 638 79, 605 84, 718	475, 137 44, 989 9, 674	342, 970 87, 247 18, 958
Total structural prod-	5, 475, 530	8, 762, 791	13, 675, 333	26, 611, 904	45, 576, 870	83, 844, 228
Nonstructural products: Stick	435, 483	128, 500	407, 470	121, 105	4, 417, 319	1, 310, 281
Powder	349, 429	410, 859	982, 078 52, 111	1,305,418	6, 416, 879	5, 956, 132
Total nonstructural	,			37, 163	95, 357	38, 013
productsGrand total	784, 912 6, 260, 442	9, 302, 150	1, 441, 659	1, 463, 686 28, 075, 590	10, 929, 555 56, 506, 425	7, 304, 426 91, 148, 654

Of the magnesium-alloy structural products sold or used, the aircraft industry took 79 percent, incendiary-bomb casings 21 percent, and other industries less than 1 percent. Of that going into the aircraft industry, 66 percent was for the manufacture of engines

Consumption of magnesium-base alloy structural products, 1941-42, by uses, in pounds

Use	1941 1942		Use	1941	1942	
Aircraft: Engine Frame Wheel Accessories Incendiary bomb casings Automotive Stationary machines	7, 943, 998 1, 358, 988 2, 878, 833 885, 666 15, 116 181, 972 45, 594	1 23, 630, 270 2, 638, 369 8, 323, 380 1, 295, 432 9, 469, 573	Portable machine equipment and tools. Textiles Foundry equipment. Oil-field equipment. Printing. Other industries. Total.	146, 427 90, 811 55, 097 2, 395 8, 293 62, 143 13, 675, 333	123, 070 222, 32 22, 34 100 71, 156 45, 576, 870	

<sup>1</sup> Includes some alloy used in the manufacture of aircraft frame, wheel, and accessories.

(including propellers), 23 percent for wheels, 7 percent for frames, and 4 percent for accessories. Sand, die, and permanent mold castings comprised 96 percent of all the magnesium-alloy structural

products sold or used in aircraft.

Fabricators of magnesium structural products increased from 38 in 1941 to 59 in 1942 and of nonstructural products from 6 to 19. By the end of 1942, 32 companies were producing sand castings, 17 permanent mold castings, 11 die castings, 3 extruded products, 3 forgings, and 20 powder. The largest producers of alloy structural products were the American Magnesium Corporation, Dow Chemical Co., Bohn Aluminum & Brass Corporation, Doehler Die Casting Co., Wright Aeronautical Corporation, Eclipse Aviation Co. (subsidiary of Bendix Aviation Corporation), Ford Motor Co., Wellman Bronze & Aluminum Co., International Silver Co., Superior Bearing Bronze Co., Stewart Die Casting Division of Stewart Warner Corporation, Hills-McCanna Co., Magnesium Products Corporation, and Dalmo Victor Co. Producers of powder included American Magnesium Corporation, California Fuel & Utilities, Inc., Imperial Paper & Color Corporation, Magna Manufacturing Co., Metals, Inc., National Fireworks, Inc., National Magnesium Corporation, New England Magnesium Co., Pilgrim Ordnance Works, Reade Manufacturing Co., Universal Match Co., and U. S. Magnesium Corporation.

## WAR MEASURES

The magnesium General Preference Order (M-2-b) now in force was originally issued on November 14, 1941, to conserve and direct the distribution of magnesium, and was to expire October 31, 1942. On October 31 the War Production Board announced that the order would continue in force until December 31, 1942. On December 31 the Director General for Operations announced a simplification of order M-2-b to bring it into line with the form of allocation orders then being issued. The amended order eliminates all references to preference ratings because the supply of magnesium and magnesium products is directly allocated to users. Provision was also made for stricter segregation of scrap in accordance with A. S. T. M. alloy designations to facilitate its handling and reprocessing.

### **PRICES**

At the request of the Office of Price Administration, Dow Chemical Co. reduced its base price of standard four-notch magnesium ingot from 22.5 to 20.5 cents a pound on January 1, 1943. Effective February 1, the Office of Price Administration, in Maximum Price Regulation 314, established 20.5 cents as the maximum price per pound for standard four-notch ingot except for sales to the Metals Reserve Co. Magnesium-alloy ingot maximum prices included in the above regulation were: Incendiary bomb alloy, 23.4 cents; 50-50 magnesium-aluminum alloy, 23.75 cents; A. S. T. M. B80-41 T No. 11 and A. S. T. M. B94-41 T No. 13, 25 cents; and all other alloys, 23 cents. On February 1, 1943, in Revised Maximum Price Regulation 125, the price of magnesium castings was reduced 3 cents a pound. Magnesium scrap and remelt ingot were controlled under the General Maximum Price Regulation during 1942, but on January 20, 1943, specific prices for various types of scrap and various grades of ingot were established under Maximum Price Regulation 302.

## FOREIGN TRADE 6

Imports of magnesium in all forms during 1942 totaled 1,386 pounds valued at \$856, of which 57 pounds were scrap from Canada; 902 pounds, alloys from the United Kingdom (magnesium content); 24 pounds, classed as sheets, tubing, ribbon, etc., from Canada; and 403 pounds, powder from Canada (257 pounds) and the United Kingdom (146 pounds). Exports of magnesium metal in primary form during 1942 aggregated 8,090,449 pounds valued at \$1,945,164, of which 7,118,469 pounds went to the United Kingdom, 971,380 to Canada, and 600 to the Union of South Africa. Comparable exports in 1941 were 3,098,424 pounds valued at \$860,486. Exports of magnesium metal in other forms during 1942 totaled 298,595 pounds valued at \$99,517, of which 265,000 pounds were consigned to the United Kingdom, 33,559 to Canada, 35 to Argentina, and 1 to New Zealand. Magnesium powder exported during 1942 totaled 43,582 pounds valued at \$66,038, of which 21,292 pounds were sent to Canada, 11,200 to Turkey, 6,380 to Australia, 2,005 to Cuba, 1,250 to China, 1,120 to New Zealand, 200 to Portugal, 72 to Iceland, and 63 to Argentina. Comparable export figures for magnesium powder and magnesium in other forms, excluding primary, are not available for 1941, as official records date only from July 1, 1941. Magnesium metal has been under export control since November 5, 1940.

## TECHNOLOGIC DEVELOPMENTS

The outstanding development of 1942 was the introduction of the ferrosilicon process 7 for extracting magnesium metal from dolomite. The process was worked out by Dr. L. M. Pidgeon of the Canadian National Research Council in 1941, and refinements were added during 1942 by engineering departments of the various companies that began using the process in 1942 and 1943. This and other methods have been described herein under Production.8 The Bureau of Mines continued to investigate the Doerner process, whereby magnesium is produced directly by electrothermic reduction of the oxide with carbon and the magnesium vapor is shock-cooled and condensed by a light oil spray; research was also continued on the direct reduction of magnesium oxide in an electrolytic cell. Pullman, Wash., the Bureau is also investigating the production of pure magnesium oxide from Washington magnesite and dolomite by the carbon dioxide leaching process.

Several extensive dolomite and magnesite deposits in the Boulder Dam area that may be used as additional sources of raw material for the Basic Magnesium (Inc.) plant at Las Vegas are described in a Bureau publication.10 At Boulder City, Nev., work was done on several methods to extract pure magnesium oxide from high-grade Nevada dolomites, and a small-scale plant has been proposed by the

<sup>6</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.
7 Stedman, G. E., Ford Makes Magnesium: Chem. and Met. Eng., vol. 49, No. 9, September 1942, pp.

<sup>134-137.</sup> Ramsay, R. H., Dominion Magnesium—Trail Blazer: Eng. and Min. Jour., vol. 144, No. 5, May 1943,

Ramsay, R. H., Dominion Magnesium—Fran Biazer: Eng. and Min. Jour., vol. 144, No. 5, May 1948, pp. 56-61.

8 Metallurgia, Magnesium and Its Production: Vol. 27, No. 161, March 1943, pp. 195-198.

9 Doerner, H. A., Holbrook, W. Floyd, Dilling, E. Don, and Harris, Dwight C., Magnesium by Electrothermic Reduction: Bureau of Mines Rept. of Investigations 3635, 1942, 47 pp.

10 Schlocker, J., Magnesium-Bearing Minerals in the Boulder Dam Area for the Production of Magnesium Metal: Bureau of Mines Inf. Circ. 7216, 1942, 16 pp.

The state of the s

大人工ないないないないでき

Bureau to be built and operated in cooperation with Basic Magnesium, Metallurgists at the Bureau's Norris (Tenn.) station are endeavoring to develop a low-cost process for extracting magnesium oxide from olivine, which occurs in large quantities in Georgia, North

Carolina, and Washington.<sup>11</sup>

All-magnesium planes have been brought within the realm of possibility by the development, after 2 years of research by engineers of the Northrop Aircraft Co., Inc., of a new welding process by which magnesium can be arc-welded in an atmosphere of helium.<sup>12</sup> "Heliarc" welding has proved successful where other welding methods have failed in dealing with high-temperature melting and heat-resisting magnesium alloys. Concise metallographic techniques most desirable for routine examinations of macro- and micro-structures in magnesium alloys have been worked out,13 and research work has led to increased knowledge of the treatment and properties of magnesium alloys. 14

The rapidly growing demand for magnesium and magnesium-base alloys has led to a great deal of research on corrosion characteristics. 15 The early belief that magnesium and its alloys were much less resistant to corrosion than other alloys in engineering use has been abandoned in the light of more precise knowledge. If cutting tools are properly designed and maintained, magnesium alloys may be machined dry with safety, as shown by current British practice. 16. Recent research has shown that silver can be plated on magnesium, after cathodic cleaning and anodic treatment of the surface, in a boric acid cyanide

electrolyte.17

Numerous patents relating to magnesium were granted during 1942, including the following: Thermal reduction of magnesium oxide with calcium carbide to produce magnesium metal and subsequent recovery from the residue and recycling of carbon and calcium carbonate (United States Patent 2,289,627); thermal reduction of magnesia in a calcined magnesia-containing ore with carbon, whereby metallic magnesium is liberated as a vapor and a molten residue is generated which exerts a washing action on the vapor and reduces the dust problem (United States Patent 2,286,209); a new method for producing magnesium-zirconium alloys in any desired shape—hitherto considered impossible (United States Patent 2,286,311); production of aluminumclad magnesium by first coating an extruded slab of magnesium alloy with zinc (United States Patent 2,301,332).

# WORLD PRODUCTION

World production of magnesium in 1942 reached an unprecedented high mark of more than 140,000 metric tons—81 percent more than the production in 1941. Although the statistical background for many

<sup>11</sup> Pawel, G. W., Olivine; Potential Source of Magnesia: Min. and Met., vol. 23, No. 426, June 1942, pp.

Gwinn, G. Richards, Olivine: Bureau of Mines Inf. Circ. 7239, 1943, 11 pp.

Paylecka, H. V., Helium-Shielded Arc Welding: Iron Age, vol. 150, No. 12, September 17, 1942, pp.

<sup>18</sup> Paylecka, H. v., Helmin-Sinctock Arc. 11 Magnesium Alloys: Met. Ind., vol. 62, No. 8, 74-76.

18 Hess, J. B., and George, P. F., The Metallography of Magnesium Alloys: Met. Ind., vol. 62, No. 8, February 1943, pp. 114-116, 136-138.

14 Fox, F. A., Some New Developments in Magnesium Alloy Technology: Metallurgia, vol. 27, No. 158, December 1942, pp. 47-50.

15 Bushrod, C. J., The Corrosion of Magnesium and Magnesium-Base Alloys: Met. Ind., vol. 61, No. 21, November 20, 1942, pp. 324-326.

16 Garner, H. Mills, Dry Machining of Magnesium Alloys: Iron Age, vol. 150, No. 4, July 23, 1942, pp. 59-54

<sup>52-54.

17</sup> Bowen, F. J., and Gilbertson, L. I., The Electro-deposition of Silver on Magnesium: Metal Finishing, vol. 41, No. 5, May 1943, pp. 271-274.

of the production figures is weak, it is estimated that about 52 percent of the output was under Axis control and 48 percent under control of the United Nations. Production in 1943 will greatly eclipse the 1942 total, and the United Nations will greatly improve their position with respect to Axis and Axis-dominated countries.

Estimated world production of magnesium, 1938-42, by countries, in metric tons

Country	1938	1939	1940	1941	1942
AustraliaCanada				200	430 230
France. Germany. Italy. Japan Norway.	1,800 14,100 102 1,500	2,500 16,500 300 2,000	2,000 25,000 500 3,000	3,000 35,000 2,500 5,000 100	3, 000 50, 000 5, 000 12, 000 2, 000
Switzerland U. S. S. R. United Kingdom United States	750 500 2, 200 2, 918	750 1,000 4,831 3,039	750 1, 500 6, 500 5, 680	1,000 4,000 12,000 14,782	1, 500 5, 000 16, 500 44, 418
Total	23, 900	30, 900	44, 900	77, 600	140, 100

Australia.—The 1,000-ton magnesium plant owned by Broken Hill Proprietary Co., Ltd., at New Castle, New South Wales, began operations in July 1941 and produced at nearly 50 percent of rated capacity in 1942. Local magnesite is ground, calcined, and reduced under vacuum with ground calcium carbide to produce magnesium metal. Attention has recently been given to the possibility of producing magnesium from the extensive deposits of dolomite at Smithton, on the northwest coast of Tasmania. Magnesite deposits in the Dial Range are also being investigated as a possible source of the metal.

Canada.—Production began in early fall of 1942 in the new ferrosilicon-process plant of Dominion Magnesium Co., Ltd., <sup>18</sup> at Haley's Station, near Renfrew, Ontario. The rated capacity, reportedly attained in February 1943, is 10 tons of magnesium a day. The retorts are charged with briquetted ferrosilicon and calcined dolomite and heated, after evacuation, by silicon carbide globars. After an 8-hour period the retorts are opened, the crystalline magnesium and the dicalcium silicate slag removed, and fresh briquets introduced immediately. The Pidgeon process is used and funds for the proving of the method up to the pilot-plant stage were furnished by Bobjo Mines, Ltd., one-third owner of Dominion Magnesium Co., Ltd. The cost of the plant (\$5,000,000) was borne by the Canadian Government, and production is supervised by Wartime Metals Corporation. Dominion Magnesium Co., Ltd., is a private concern incorporated to build and operate the plant without fee or profit.

Exclusive Canadian and United States rights to the Blackwell-Turner high-frequency induction process for the production of magnesium have been granted to the International Industrial Research Corporation of Freeman, Ontario, by the Lancashire Metal Subliming Corporation, Ltd., of Liverpool, England. Plans are to produce the metal from olivine or serpentine at a point near adequate ore deposits and power. Facilities are also planned for the production of magnesium castings, extrusions, forgings, and sheet. Magnesium Devel-

<sup>18</sup> Ramsay, R. H., Dominion Magnesium—Trail Blazer: Eng. and Min. Jour., vol. 144, No. 5, May 1943, pp. 56-61.

opment Co., Ltd., was formed in 1942 under a British Columbia charter with an authorized capitalization of 100,000 shares at a par

value of \$1 a share.


France.—Output of magnesium is controlled by the Pechiney, Ugine, and Bozel-Maletra concerns, which produce the metal from dolomite and Mediterranean sea-water brine. Production is reportedly being expanded with active cooperation of the Germans, who are supplying funds through the Aero-Bank, the Paris branch of the German Bank für Luftfahrt, A. G.

Germany.—Deutsche Magnesit, A. G., founded in 1929 at Salzburg, has been transferred to Munich, where its magnesium-production activities will be associated with those of Oesterreichische Magnesit, A. G. A new research organization will be formed jointly with I. G. Farbenindustrie, A. G., and will be known as Studiengesellschaft für Metallgewinnung, G. m. b. H. This research group will study the patents of J. März covering thermal reduction of calcined magnesite by carbon and by calcium carbide. Germany has two main sources for the production of metallic magnesium at its disposal—the potash mines in Hanover and Saxony and the magnesite deposits in Bavaria and Austria. These sources can supply all the raw material that the expanded German magnesium industry can use; the limits on expansion are thus not due to a raw-material shortage but to shortages of labor, power, and equipment.

Hungary.—According to a report from the official German news agency, the Hungarian State Iron, Steel, and Engineering Works has obtained a license from I. G. Farbenindustrie, A. G., for the production of metallic magnesium. The new works, the location of which has not been announced, will be operated by a company known as the Hun-

garian Magnesium & Elektron Co.

United Kingdom.—The Lancashire Metal Subliming Co. is reported to have started the production of magnesium from magnesite using a direct thermal reduction of the oxide. Calcined magnesite is mixed with a reducing agent and heated by high-frequency induction coils to a temperature above the sublimation point of the metal. The metallic vapor is then collected and crystallized under reduced pressure. The Minister of Aircraft Production issued Magnesium Control Order 4 late in 1942, providing a standardized price for all unfabricated magnesium and magnesium alloys and reducing the price of powder to 4s. a pound for all grades. Controlled prices for billets and slabs were also specified.



# **ANTIMONY**

By A. L. RANSOME

### SUMMARY OUTLINE

	Page		Page
Summary	 781	Domestic consumption	. 787
Salient statistics	 782	Prices	788
War agency regulations	 . 783	Foreign trade	789
Domestic production		World production	. 791
Mine output	 784	Review by countries.	792
Smelter output	 785		
Secondary production	787		

### SUMMARY

Under the use limitations in effect during 1942 the total supply of antimony in all forms, although less than in 1941, was more than adequate to meet military and essential civilian requirements. As in 1941, the supply came largely from Mexico and Bolivia. Imports were augmented by a greatly increased domestic production that helped measurably in alleviating a rather tight situation. By the first part of 1943 stocks had been built up to the point where antimony was classed as a material available in sufficient quantity to be used as a substitute for more critical metals in the strategic minerals list.

The relatively high price for ore in effect at the end of 1941 continued with but little change throughout 1942, owing largely to informal Government control through the Office of Price Administration. The 50- to 55-percent ores quoted at \$2.00 to \$2.15 per shortton unit, New York, at the beginning of 1942 were priced at \$2.10 to \$2.20 at the close of the year. The quotation for domestic metal—14.00 cents per pound, New York, on January 1, 1942—increased to 16.049 cents by the end of the year. This latter figure includes the 3-percent excise tax effective December 1, 1942. The average price of 15.55 cents in 1942 compares with 14.00 cents for both 1940 and 1941

Domestic production of antimony ore increased 102 percent over 1941, and the metal content gained 143 percent—an indicated rise in the average grade from 35 percent in 1941 to 42 percent in 1942. The antimony content of antimonial lead produced from all classes of foreign and domestic ores increased 10 percent over the 1941 figure and was the largest recorded since 1928. The contents of the total production of antimonial lead at primary refineries from all raw materials—scrap and domestic and foreign ores—increased less than 1 percent but was still the largest since 1929. Although primary antimony available for consumption decreased 20 percent, actual consumption of antimony, including primary material and antimony recovered from the treatment of scrap, was probably the same or even

THE PROPERTY OF THE PARTY OF TH

THE REPORT OF THE PARTY OF THE

somewhat more than in 1941. Stocks of metallic antimony at producers' plants, as reported to the Bureau of Mines, decreased from 730 tons on December 31, 1941, to 477 tons on December 31, 1942—a continuation of the down trend noted in 1941. A small increase in metal production at the Kellogg (Idaho) electrolytic plant augmented by an appreciable addition to the total supply from the new electrolytic plant at Big Creek (Idaho) was insufficient to offset a slight decline




FIGURE 1.—Trends in world production, 1910-38, and United States imports and New York price of antimony, 1910-42.

in the much greater output at Laredo, Tex. No metal was produced by the Los Angeles smelter in 1942.

Figure 1 shows trends in world production from 1910 to 1938 and United States imports and prices from 1910 to 1942.

Salient statistics for antimony in the United States, 1938-42

	1938	1939	1940	1941	1942
Production of antimony ore and concentratesshort tons Antimony cortainedshort tons	2, 730 650	3, 174 393	1, 124	3, 460	6, 980
Antimony content of antimonial lead produced from domestic	000		494	1, 214	2, 944
and foreign oresshort tons_	2,080	1,108	2,077	2, 958	3, 267
Secondary antimony produceddodo	8, 500	9,810	11, 421	21,629	18, 200
Imports for consumption:	-,	1,111	,	,,	,
Antimony in oredo	8, 322	9.448	15, 733	19, 386	20, 946
Needle or liquidated antimonydodo	90	228	113	638	522
Metaldo	821	1,045	209	7, 469	127
Oxidedo	414	167	203	1, 100	1
Exports of foreign antimonydo	711	58	276	70	(1)
Primary antimony available for consumptiondo	11. 557	11, 609	17, 955	29, 994	23, 852
Stocks of antimony in bonded warehouse at end of year	11, 557	11, 009	17,900	29, 894	20, 802
short tons	345	685	3, 417	416	(3)
Average price of antimony at New York: 3	010	000	0, 111	110	(-)
Chinesecents per pound	14, 59	14.44	4 16, 50	4 16, 50	4 16, 50
	12.35	12.36	14.00	14.00	15. 55
World productionshort tons_	<b>35, 4</b> 00	(²)	(²)	(2)	(2)

<sup>&</sup>lt;sup>1</sup> Less than 1 ton.

<sup>&</sup>lt;sup>2</sup> Figures not yet available.

<sup>3</sup> According to American Metal Market.
4Nominal.

### WAR AGENCY REGULATIONS

The most outstanding effect of Government control on the antimony industry during 1942 was indicated by the reclassification of antimony from group II to group III of the Material Substitutions and Supply List of strategic minerals, effective February 1, 1943. As compiled by the War Production Board, Conservation Division, this list, divided into three groups, reflects the relative essentiality and the current relative supply status of materials useful to the war program. Group I includes critical materials, supplies of which are insufficient for existing war demands; group II—essential war materials, supplies of which are in balance with immediate demand; group III materials available in significant quantities, which are particularly recommended as substitutes for critical materials.

On March 30, 1942, allocation control over antimony was ordered by the Director of Industry Operations of the War Production Board. with issuance of General Preference Order M-112, effective May 1. Under this order deliveries of antimony were strictly controlled, and all forms of antimony (except alloys containing less than 50 percent by weight of antimony) were placed under complete allocation. Subsequently on July 11, 1942, Order M-112 was amended to allow up to 50 tons a month of contained antimony in ore or concentrates to be delivered by domestic producers, including Alaskan producers, without restriction. Order M-112 was again amended on March 8, 1943. No change was made in the 50-ton limit on the permissible antimony content of unallocated ores and concentrates, but the limit on unallocated deliveries of antimony metal and alloys (50 percent or more antimony contained) was raised from 25 pounds to quantities up to 2,240 pounds. Restrictions were also relaxed to permit the use of greater amounts of antimony in battery grids, in nonacid resisting enamels, and in other antimonial lead uses. An additional indirect curtailment in the use of antimony was effected by the War Production Board Order M-38-c of January 10, 1942, which restricted the use of lead. This order was subsequently relaxed because of the easier supply position.

Because of informal Government control through the Office of Price Administration, the price of antimony showed no change during 1941 and the first months of 1942. The price of 14.00 cents per pound, New York, in effect at the beginning of 1942 was allowed to advance to 15.955 cents on March 23 for small case lots; this was subsequently adjusted upward to meet an advance in freight rates. On April 28, antimony metal was placed under the General Maximum Price Regula-Effective December 1, a 3-percent excise tax was placed upon property transportation, and being payable by the consumer the quoted price of 16.049 cents reflected this action.

On April 7, 1942, the Metals Reserve Co. agreed to resell antimonv ore imported from Bolivia in accordance with a schedule of prices acceptable to the Office of Price Administration. Similarly, on April 27 the War Production Board, in cooperation with the Office of Price Administration, worked out a schedule of informal maximum prices for importers of Mexican antimony ore who applied to the War Production Board for import licenses. Effective May 11, 1942, antimony ores and concentrates were excepted from the General Maximum Price Regulation.

# DOMESTIC PRODUCTION MINE OUTPUT

Output from 31 operating antimony mines in 1942 more than doubled that of 1941 from 37 properties and established a new record. The marked gain was due almost entirely to increased output from the Yellow Pine mine in Idaho. In addition, mines containing ores that are produced principally for their value in other metals, mainly gold, silver, copper, and lead, have augmented the supply of antimony for domestic consumption. A large proportion of this increased supply in 1942 resulted from the operations of the Bunker Hill & Sullivan Mining & Concentrating Co. plant at Kellogg, Idaho, and the new Sunshine Mining Co. plant at Big Creek, Idaho.

In 1942, 6,980 short tons of material, containing 2,944 tons of antimony, classed as antimony ores and concentrates were produced compared with 3,460 tons containing 1,214 tons of antimony in 1941. Upon the basis of antimony content the record total for 1942 was 143 percent higher than in 1941 and 40 percent above the previous record

of 2,100 tons produced in 1915.

Alaska.—The Stampede mine, Kantishna district, was the only antimony property reporting shipments in 1942. Although the mine was reportedly acquired by Earl Pilgrim early in 1942 from Morris P. Kirk & Son, Inc., production data for 1942 were submitted by Kirk

as owner and operator.

Several other antimony properties were prospected and developed in 1942, but no definite figures on production or shipments, if any, were obtained. The Hi Yu Mining Co. was reported to be developing a deposit on Fairbanks Creek near Fairbanks, and a property owned by Sam Gamblin at the head of Tok River reportedly has a good showing of stibnite ore.

In the latter part of the year the first shipment of antimony ore, amounting to 16 tons assaying 38.09 percent antimony, was received at the Fairbanks purchasing depot of the Metals Reserve Co. operated

by the Territorial Department of Mines.

California.—The Bishop mine in Inyo County produced and shipped antimony ore in 1942. Smaller shipments came from two additional properties in Inyo County and two in San Benito County. Some ore was produced in less than 1-ton lots.

Production for the State amounted to 68 tons of ore containing 29 tons of antimony, an increase over the 51 tons of ore containing about

15 tons of antimony in 1941.

Idaho.—Not only was Idaho the principal producer of antimony ores and concentrates in 1942, but the total was greater than the entire United States output for any previous year. It amounted to 6,225 tons containing 2,715 tons of antimony; the Yellow Pine mine, owned and operated by the Bradley Mining Co., produced 5,950 tons containing 2,597 tons of antimony. This mine is the largest single source of the metal in the United States. The Antimony Ridge mine, owned and operated by United Mercury Mines, is the second-largest antimony property in Idaho and took second place in the United States in 1942.

In addition to antimony ore, large amounts of antimony came from ores classified as silver ores, copper ores, and others not included in this report as mine output of antimony. The Coeur d'Alene Mines

いからないていてはなるないまとれてあるとなるとはないはよれていているとはない

ということというないないというないからいっというとうない

Corporation of Burke and the Sunshine Mining Co. of Kellogg, both produced substantial tonnages of approximately 20-percent antimony concentrates from silver-copper-antimony ore. Production from the former was shipped to the Bunker Hill smelter, whereas concentrates from the latter were treated at the company electrolytic plant built in 1942 for the express purpose of processing such material into antimony metal.

Montana.—Production of antimony ores in Montana increased in 1942 to 280 tons containing 51 tons of antimony from the 1941 total of 113 tons containing 43 tons of antimony. This gain is due largely to the development, by the Sunshine Mining Co., of the Burns antimony district, Sanders County, between Burke, Idaho, and Thompson Falls, Mont. This district embraces a wide section of the Bitterroot Range at the head of Prospect Creek, the main mineralized outcrop occurring along a flat-bedded structure for several miles. Until acquired by Sunshine, under lease, the Prospect Creek deposits had been prospected sporadically for several years with only partial success. Mines and claims reported to have been active were the Stibnite Hill, Eureka, Ellis, and Interstate.

Nevada.—Although the number of reportedly active antimony properties was less than in 1941, the total was greater than in any other State. Nearly every section of the State was represented; and the producing counties, in order of descending importance in 1942, were: Pershing, Nye, Washoe, Lander, Humboldt, and Mineral. There were 11 producers of more than 1 ton; but the average size of the operations was small, and the average grade of the ore was low. Total 1942 production for the State was 305 tons containing 96 tons of antimony—a drop from the 1941 total of 691 tons containing 146 tons of antimony. Oregon.—Production and shipments of antimony ore in 1942 were

made from the Jay Bird mine in Jackson County and the Gray Eagle (Koehler) mine in Baker County. The latter property, in the Virtue

district near Baker, was a producer during World War I.

Washington.—The Lucky Knock mine in Okanogan County was the only property to report production and shipment of antimony ore in 1942.

#### SMELTER OUTPUT

In 1942 primary antimony for shipment to others was produced from foreign and domestic ores at three plants in the United States: Bunker Hill & Sullivan Mining & Concentrating Co., Kellogg, Idaho; Sunshine Mining Co., Big Creek, Idaho; and Texas Mining & Smelting Co., Laredo, Tex. In addition, metallic antimony was again produced by the American Smelting & Refining Co. at its Omaha (Nebr.) plant. This material was used for conversion into other products and was not sold as metal.

The Harshaw Chemical Co. produced no antimony metal at its El Segundo (Calif.) plant in 1942, the output being restricted to antimony oxide. In September 1942, the full-size electrolytic antimony plant of the Sunshine Mining Co., under construction earlier in the year, went into limited operation. This followed the successful experimental operation of a pilot plant from December 1, 1940, to June 1, 1942. Although the plant capacity is rated at approximately 100 tons of metal a month, production by the end of 1942 and during the first quarter of 1943 had not reached capacity owing to a shortage of under-

ground labor at the company mines. The greater proportion of the output is from antimony concentrates from tetrahedrite ore, the bal-

ance being from company-mined low-grade stibnite ore.

Imports of antimony ore in 1942 amounted to 50,021 short tons containing 20,946 tons of antimony compared with 41,662 tons in 1941 containing 19,386 tons of metal, an increase of 8 percent in terms of antimony content. Industrial receipts of foreign antimony in the United States in 1942 amounted to 48,005 tons of ore compared with 40,434 tons in 1941. These totals are 96 and 97 percent of the total amount imported. The difference in each instance can be accounted for by the usual lag between reporting imports on one hand and receipts on the other, plus the variable tonnage of material in transit at the end of the year which is not statistically counted in the receipts on that date. Receipts exceeded consumption in 1942, and stocks of antimony ore increased 67 percent (gross weight). In 1941 the reverse was true, and stocks decreased 56 percent. Receipts gained 19 percent over 1941, and consumption of 44,944 tons (containing approximately 20,000 tons of antimony) in 1942 was 3 percent less than the reported consumption of 46,211 tons (containing 20,530 tons of antimony) in 1941. The following table shows industry stocks, receipts, and consumption of foreign antimony ore upon the basis of gross weight.

Consumption and stocks of foreign antimony ore in the United States, 1940-42, gross weight in short tons

	1940	1941	1942
Stocks at beginning of year Received during year Consumed during year Stocks at end of year	7,775	10, 323	4, 546
	34,530	40, 434	48, 005
	31,982	46, 211	44, 944
	10,323	4, 546	7, 607

Production of antimonial lead at primary refineries is shown in the accompanying table. The figures cover only part of the total antimonial lead production, as large quantities are produced at plants that operate exclusively on scrap, and some hard lead is made by mixing antimony and soft lead.

Antimonial lead produced at primary lead refineries, 1938-42, in short tons

		Antimony content						
Year Productio	Production	From do-	From for-	Them gover	Total			
		mestic ores e	eign ores 1	From scrap	Quantity	Percent		
1938 1939 1940 1941	24, 123 21, 995 29, 762 40, 237 51, 762	1, 871 929 1, 915 2, 586 2, 396	209 179 162 372 871	729 923 867 552 257	2, 809 2, 031 2, 944 3, 510 3, 524	11. ( 9. 9. 9. 9. 8. 7 6. 8		

<sup>&</sup>lt;sup>1</sup> Includes lead ores, antimony ores, and metallic antimony.

一方 大学の情報の表情なるないとう

- Action Control of the Control of t

# SECONDARY PRODUCTION

A large part of the total antimony available for consumption each year in the United States is recovered in the treatment of secondary nonferrous metals. The production of antimony from secondary metals in 1942 totaled 18,200 tons—a 16-percent decrease from the 21,629 tons produced in 1941. Primary antimony available for consumption in the United States in 1942 totaled 23,852 tons. antimony available was therefore 42,052 tons, including 57 percent primary and 43 percent secondary; comparable proportions in 1941

were 58 and 42 percent.

Refined metallic antimony is rarely, if ever, produced from scrap metals, the output being in the form of lead-base and tin-base alloys. Most of the plants treating scrap metals containing antimony consumed some other antimony materials, including antimony ore or metallic antimony, for the purpose of adjusting the antimony content of the products. Much of the production is in the form of antimonial lead returned directly to the storage-battery trade. Antimony oxide, sodium antimonate, and other compounds are also produced from scrap metals. Additional information on secondary antimony is given in the chapter on Secondary Metals-Nonferrous.

# DOMESTIC CONSUMPTION

Data on the consumption of primary antimony in the United States, based upon quarterly surveys conducted by the Bureau of Mines in 1942, are not yet available in complete form summarizing the entire Upon completion this information will be published in a supplemental release. However, an approximate idea of the trend of consumption can be obtained from the following table, which shows the annual supply available for consumption.

Primary antimony available for consumption in the United States, 1938-42, in short tons 1

	1938	1939	1940	1941	1942
Domestic antimony recovered in antimonial lead	1,871	929	1, 915	2, 586	2, 396
Antimony ore- Needle or liquated 2.	8, 322 63 336	9, 448 160 138	15, 733 79	19, 386 447	20, 946 365 (4)
Components - Type metai, etc Regulus	355 821	121 1,045	191 209	202 7, 469	35 127
Total available Exports under draw-back	11,768 211	11, 841 232	18, 131 176	30,092 98	23, 869 8 17
Available for consumption 6	11, 557	11,609	17, 955	29, 994	23, 852

<sup>1</sup> Excludes domestic antimony recovered as miscellaneous alloys, oxides, and other compounds.
2 Content estimated at 70 percent.
3 Content estimated at 80 percent.

Primary antimony available for consumption in 1942 decreased 20 percent below the total for 1941 but was 33 percent over 1940. Imports of ore continued to advance; and domestic production, even though still comparatively small, increased to more than twice the

<sup>4</sup> Less than 1 ton.
5 January to June, inclusive.
6 Figures are low owing to somewhat incomplete data concerning some items of domestic production.

1941 total in terms of antimony content. Data on the amount of antimonial lead used in making storage batteries during 1942 are not yet available. This battery metal so used, containing 4 to 12 percent antimony, probably was less than the 131,000 tons consumed in 1941 as reported by the American Bureau of Metal Statistics. Most of the antimony recovered in battery metal is from scrap, though a substantial amount of new metal is added to raise the alloy to the required antimony content.

An important use of antimony is in white-base antifriction bearing metals. According to the Bureau of the Census, shipments of this material produced for sale and for plant consumption in 1942 totaled 22,091 tons—a 33 percent decrease from 33,146 tons in 1941. The manufacturers reporting data that give the above totals represent almost the entire industry. As is true of so many metals during the present war, the decreased consumption does not necessarily indicate lessened importance; rather it reflects relative scarcity of materials

coupled with regulatory conservation measures.

Less antimony was used in making chemicals in 1942 than in 1941, the production of oxide and other compounds decreasing 18 percent to 11,950 short tons (preliminary figure) containing approximately 9,703 tons of antimony. Figures on the production of compounds in the 4 preceding years, with the estimated antimony content in parentheses, are as follows: 1941, 14,588 tons (11,590); 1940, 10,211 tons (8,223); 1939, 7,668 tons (6,188); 1938, 4,393 tons (3,539). Nearly all this material was made from foreign ores. Oxide, the most important compound, is used extensively in paints, lacquer, synthetic enamel, porcelain enamel, and glass. A rapidly growing use for oxide, particularly as a war material, is the treatment of canvas and other textiles against rotting and fire.

# **PRICES**

The price of domestic brands of antimony was quoted at 14.00 cents a pound for less than carlots in New York during January and February 1942, the same as throughout 1940 and 1941. On March 23 the quotation was listed at 15.955 cents by authority of the Office of Price Administration. Effective April 13, the price was adjusted to 16.013 cents to meet a 6-percent advance in freight rates, and this adjusted price remained unchanged until December 28, when the quotation was raised to 16.049 cents to include the 3-percent excise tax on transportation effective December 1 and payable by the buyer for delivered metal. These prices were still unchanged by the end of May 1943. The average 1942 price for domestic antimony was 15.55 cents (l. c. l. ex store, New York). Very little Chinese metal was available in 1942, and the quotation of 16.50 cents, in effect since November 1939, remained unchanged in 1942 and was the same at the end of May 1943; the price was nominal.

Prices for English regulus (minimum, 99 percent antimony) and foreign regulus (spot deliveries from warehouse) remained unchanged throughout 1942 at £120 and were the same at the end of May 1943.

Control of the second of the s

子がなるというというなの様にかけることのできるというだろ

Average monthly quoted prices of antimony, prompt delivery at New York, 1938-42, in cents per pound

Month	C	Chinese brands (duty paid) 1					American brands 2			
	1938	1939	1940 3	1941 3	1942 3	1938	1939	1940	1941	1942
January February March April May June July August September October November December	15. 56 15. 74 15. 75 15. 65 14. 46 13. 94 14. 00 14. 00 14. 00 14. 00 14. 00	14. 00 14. 00 14. 00 14. 00 14. 00 14. 00 14. 00 14. 00 14. 00 14. 24 16. 50 16. 50	16. 50 16. 50	16. 50 16. 50	16. 50 16. 50	13. 75 13. 75 13. 75 13. 65 12. 46 11. 73 11. 02 10. 88 11. 32 12. 06 12. 25 11. 56	11. 68 11. 25 11. 27 11. 50 11. 70 12. 00 12. 00 12. 87 14. 00 14. 00 14. 00	14. 00 14. 00 14. 00 14. 00 11. 00 14. 00 14. 00 14. 00 14. 00 14. 00 14. 00	14. 00 14. 00	14. 0 14. 0 14. 6 15. 9 16. 0 16. 0 16. 0 16. 0 16. 0
Average	14. 59	14. 44	16. 50	16. 50	16. 50	12. 35	12.36	14.00	14.00	15. 5

<sup>&</sup>lt;sup>1</sup> From daily issues of American Metal Market, except 1938 and 1939, which were taken from Metal Statistics, 1940, p. 529.

<sup>2</sup> Metal Statistics, 1943, p. 543.

<sup>3</sup> Mominal.

Quotations for antimony ore on January 1, 1942, according to E&MJ Metal and Mineral Markets, were as follows: "Per (short-ton) unit of antimony contained, at New York, 50 to 55 percent, \$2.00@ \$2.15;58 to 60 percent, \$2.15@\$2.25;60 to 65 percent, \$2.25@\$2.35. London, 60 to 65 percent, 14s. 9d. per long-ton unit." These prices fluctuated slightly throughout the first months of 1942 but by April steadied to \$2.15@\$2.20, \$2.20@\$2.30, and \$2.30@\$2.40 for the lower, intermediate, and higher grades at which they remained until December. Prices were lowered slightly in December, the quotations being \$2.10@\$2.20, \$2.15@\$2.20, and \$2.20@\$2.30 for the three different grades. These were unchanged by the end of May 1943. The London price for the higher grade ore decreased from the opening quotation to 12s. 6d. by August, advanced slightly to 12s. 9d. in September and decreased again to 12s. 6d. in October, at which point it remained unchanged by the end of May 1943. Prices were nominal.

# FOREIGN TRADE 1

The following tables show imports and exports of antimony and antimony products.

Antimony imported for consumption in the United States, 1938-42

	Antimony ore		y ore	Needle or liquated anti- mony		Antimony metal		Antimony oxides and other compounds	
Year	G14	Antimony content							
	Short	Short tons	Value	Short tons	Value	Short tons		Short tons	Value
1938	19, 811 21, 000 37, 966 41, 662 50, 021	8, 322 9, 448 15, 733 19, 386 20, 946	\$1, 095, 497 1, 132, 359 2, 027, 612 2, 717, 472 3, 947, 772	90 228 113 638 522	\$12,016 30,102 19,464 126,018 101,164	821 1, 045 209 7, 469 127	\$155, 420 196, 812 50, 048 2, 056, 678 28, 910	420 173 5 2	\$94, 400 29, 786 1, 851 537

<sup>1</sup> Less than 1 ton.

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Antimony imported for consumption in the United States, 1941-42, by countries

		Antimony or	э ′	Antimony metal	
Country	Gross weight	Antimon	y content	Short tons	Value
	(short tons)	Short tons	Value	Short tons	V alue
Belgium 1941 • •				22	<b>\$4, 24</b> 8
BoliviaBurma	11, 695 30	7, 094 18	\$1, 210, 118 3, 673 145		
China Costa Rica Honduras	2 28 24	1 17 11	2, 250 1, 970	7, 115	1, 950, 990
MexicoPeru	1, 177	11, 664 581	1, 399, 896 99, 420	328 4	100, 309 1, 131
	41, 662	19, 386	2, 717, 472	7, 469	2, 056, 678
1942				108	24, 132
Belgium-Luxemburg Bolivia Canada	12, 112 1, 678	7, 355 861	1, 985, 401 212, 229		
Guatemala Honduras Mexico	25 125 35, 491	13 80 12, 302	3, 500 15, 145 1, 693, 193		
Peru United Kingdom 1	590	12, 302 335	38, 304	19	4, 778
	50, 021	20, 946	3, 947, 772	127	28, 910

<sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

Estimated antimony content in type metal, antimonial lead, and other alloys imported for consumption in the United States, 1938-42, in short tons 1

					14 to 1 to 1 to 1 to 1	N 15 W	
• Year	Type metal and anti- monial lead	ollove 2	Total	Year	Type metal and anti- monial lead	allove 2	Total
1938	<b>3</b> 59	296	355	1941	202		202
1939	59	62	121	1942	35		35
1940	191		191				

<sup>&</sup>lt;sup>1</sup> For details of gross weight and values, see imports shown in Lead chapter of this volume. <sup>2</sup> Chiefly in special antimony-lead alloys containing high percentage of antimony. <sup>3</sup> Type metal only.

# Foreign antimony (regulus or metal) exported from the United States, 1938-42

Year	Short tons Value Year		Short tons	Value	
1938 1939 1940	711 58 276	\$96, 836 16, 736 75, 440	1941 1942	(¹) 70	\$19, 690 181

<sup>!</sup>Less than 1 ton.

Imports of antimony ore in 1942 again came principally from Mexico and Bolivia. The total from Mexico was 24 percent more than in 1941, and Bolivian exports to the United States gained nearly 4 percent. The small tonnage of needle or liquated antimony, credited from China, came from bonded warehouse, as there was no actual importation of Chinese antimony in 1942.

In addition to the exports of foreign metal reported in the last table above, 17 tons were exported in finished products under the draw-

The second secon

back provisions of the tariff law from January to June, inclusive; draw-back exports amounted to 98 tons in all of 1941 and 176 tons in 1940.

# WORLD PRODUCTION

Data on world production of antimony during the war years since 1938 are incomplete, although additional information has become available for 1939 and 1940 since the figures were last published in the Antimony chapter, Minerals Yearbook, Review of 1940. Although data from countries that supplied 54 percent of the world total in 1938 indicate an 86-percent increase over that year in total world production during 1942, estimates by the Bureau of Mines place the total world mine production of antimony during 1942 at about 50,000 short tons (recoverable antimony content in ores mined). Of this amount the United Nations controlled or had access to approximately 70 percent.

World production of antimony, 1937-42, by countries, in metric tons 1 [Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
North America:						C # 1 (1) 7
Canada	2 18	34	8 550	1,083	1, 329	1, 263
Honduras	- 10	34	- 550	(4)	23	(4)
Mexico 5	9, 788	7, 391	7, 243	11, 286	10, 241	10, 759
United States	1,056	542	328	412	1, 013	2, 457
South America:	1,000	342	323	412	1,013	2,401
South America: Argentina. Bolivia (exports) Peru.	31	174	97	91	107	(4)
Rolivia (avnorte)	6,556	8, 682	9, 255	10. 813	13, 680	16, 231
Ports	1,296	753	775	809	1,440	* 1, 430
Europe:	1, 200	100	110	800	1,440	• 1, 450
Czechoslovakia	997	\$ 800	\$ 1,012	3 1, 104	1, 645	(4)
Germany (Austria)	200	145	(4)			
Greece	200	140	(9)	(2)	1 23	X
ltaly	414	740	(4)	(4)	1 23	ΣX
Portugal	49	131	174	247	999999	X
Portugal Spain	35	44	172	137	l Σ	33
Yugoslavia	1.447	2, 739	3, 337	\$ 4,860	23	33
Asia:	1,447	2, 109	0,001	4,800	(5)	(3)
Borneo, British	4		14	41	(4)	145
Burma	. 28	84	(4)	(4)	1 22	1 22
China 6	14,702	7, 797	6,497	5, 493	1 12	<u>₩</u>
Chosen	14,702	(4)			0000	23
India, British	, °	(9)11	(4)	(4)	8	\ \X
Indochina.	5	83	19	(4)	l Σ	ತಾತಾತಾ <b>ತ</b>
Turkey (Asia Minor)	536	398	460	7 264	(4)	1 12
A #=2	200	990	400	204	(9)	(r)
Africa: Algeria	778	744	(4)	(4)	(4)	8 137
	110	/111	(3)	(-)	(9)	- 137
French	20	125	(4)	(4)	m	8 72
Spanish	158	93	(4)	64	8	(4) 12
Southern Rhodesia	64	63	50	(4)	1 12	$\mathbf{x}$
Union of South Africa.	04	10	8	126	324	(*)
Oceania:		10	0	120	* 324	325
Australia:			i i		1 1	
New South Wales	13	12	7	9	128	(A)
Queensland	(10)	8	1	8	25	X
Victoria	145	195	100	14	25 15	<b>.</b>
Western Australia	3 245	324	296	214	297	X
New Zealand	- 240	324	290	1	297	$\mathcal{R}$
TION TOWNSHITT		1		1	8	(7)
*** ***	38,600	32, 100	(4)	(4)	(1)	(4)
	50,000	J2, 100	(2)	(+)	(9)	(-)

<sup>&</sup>lt;sup>1</sup> Approximate recoverable metal content of ore produced exclusive of antimonial lead ores. 92 percent of reported gross content is used as basis for calculations in nearly every instance. Japan produces antimony but data on production are not available.
<sup>2</sup> Recoverable metal content of concentrates exported.

Estimated. Data not available.

10 442 kilograms.

Includes antimony content of antimonial lead.

Figures represent antimony content of regulus, crude antimony, and oxide exported.

January to April, inclusive.
 January to October, inclusive.

### REVIEW BY COUNTRIES

Algeria.—Antimony has been found in several localities in the Department of Constantine in Algeria, but reserves are meager. The most important mine is the Hamminate-Sanza, 19 miles southeast of Constantine. The Taya-Khenez mine, 25 miles east of Constantine, ranks second in antimony production. Both of these properties are controlled by the Soc. Nouvelle des Mines de la Lucette. Although potential monthly production of concentrates has been estimated at 200 tons, production for the first 4 months of 1942 was only 331 tons, averaging 35 percent antimony.

Argentina.—Antimony production in Argentina is small, and production figures for 1942 are not available. Part of Argentina's supply of antimony is secured as a byproduct of the lead ores imported from Bolivia. Mines are small and in the mountains of Jujuy and La

Rioia Provinces.

Australia.—The March 1943 issue of Mineral Trade Notes, published by the Bureau of Mines, gives the most recent available information on the antimony industry in Western Australia. The section concerning antimony is quoted in full:

The lode carrying antimonial ore at the Wiluna mines, the chief producer of antimony in Western Australia, is nearing depletion, and other sources are being sought. Many antimony occurrences have been examined but were found suitable only for individual operations. The Blue Spec mine, 15 miles east of Nullagine, offers prospect of reasonable production; and the Federal Government, on recommendation of the State Government, has advanced the company £A15,000 for expanding operation. The mineralized area is 11 miles long and has been opened at a number of places, six localities showing good shoots of antimonial ore. Reserves of proved and probable ore total 17,000 long tons averaging 17 dwt. of gold a ton and 3 percent antimony. The antimonial concentrate obtained assayed 56 percent antimony and 5.5 ounces of gold. The company plans to sink a new main shaft 300 feet deep and open a new level. An adjoining lease will be developed.

Bolivia.—Mining for antimony in Bolivia started as early as 1903, and since that time Bolivia has become the world's second largest producer. The antimony deposits are scattered throughout various Provinces, with the most important near Tupiza in the Department of Potosí and Challapata in the Department of Oruro. Most of the mines are small and are worked intermittently by individual oper-

ators depending largely upon the market price of the ore.

Exports of antimony in 1942 reached 17,642 metric tons (content in ore) as compared with 14,870 tons in 1941. On March 18, 1942, the Metals Reserve Co. of the United States contracted with Bolivian antimony producers for all antimony and antimonial lead concentrates produced from February 1 to December 31, 1942, except for material sold to Great Britain and Argentina and for domestic consumption in Bolivia. The established price ranged from \$1.85 to \$2.21 a shortton unit, f. o. b. Pacific ports, depending on the grade of ore. Exports of concentrates to the United States through the Antofagasta consular district during the first 11 months of 1942 totaled 7,960 metric tons.

Canada.—The Austin Antimony Syndicate reportedly drilled its property south of Wabigoon, Ontario, in 1942 in a search for antimony. The deposit, originally trench-sampled for gold, showed a 10-percent stibnite content, and assays of more recent samples show even a higher antimony content. Bulk samples were shipped to Haileyburg for testing by the Wah Chang Corporation in New York. The deposit is

approximately 250 feet long and about 10 feet wide.

いてんとか、またとうなが、 はおおうと おおとのとないないというというないと

- 156 DEJ

China.—China reportedly still has under its control the bulk of the antimony mines that in pre-war years made it the largest producer of antimony in the world. Official Chinese statements indicate that the annual production amounts to about 7,500 tons. A plan mapped out in 1940 by the Ministry of Economic Affairs provided for the production of 1,000 metric tons of antimony in the Szechwan-Sikang area in 1940 and for 1,500 in 1942. With the closing of the Burma Road early in 1942, contract antimony shipments to the United States through the Metals Reserve Co. stopped. Presumably some metal has been getting through to Russia, although no data indicating the extent of such trade are available.

Cuba.—Antimony occurs in the MacKinley area in the northwestern part of the Isle of Pines, and should the need for antimony become great enough to warrant prospecting and mining of the ore this deposit could be developed. The Gaudalupe mine about 13 miles west of Nueva Gerona on the Isle of Pines was originally located for gold about 20 years ago. No work was done, and the claim lapsed. The same area was relocated in 1939 for antimony. The Antimony Co. of Cuba, S. A., was formed, but only a few tons of surface ore were mined. It is reported that \$70,000 has been spent in development since February

1941.

Honduras.—Mineral Trade Notes, September 1942, published by the Bureau of Mines, gives the following information concerning antimony developments in Honduras:

Casa Uhler, S. A., shipped 5 tons of antimony ore to the United States in February. Ore was obtained from the property of Sr. Hector Lainez at Suyatel, approximately 50 kilometers from Tegucigalpa. Casa Uhler, S. A., has contracts with other suppliers and will make additional shipments in the future.

India.—Exploration within the past 2 years has revealed sources of antimony in India sufficient to justify the installation of a plant to

treat and refine the ores.

Japan.—The latest information available is that Japan proposed a semigovernmental antimony company to increase production. This was necessary because Japan produces only a fractional amount of antimony to meet its needs and Bolivian exports to Japan had been cut off.

Mexico.—Mexican production of antimony in 1942 amounted to 11,695 metric tons contained in antimony ore and a small quantity of antimonial lead ore, a 5-percent increase over the 1941 total of 11,132 tons. Exports in 1942 totaled 11,283 tons compared with 10,734 tons in 1941.

A detailed description of the antimony deposits and mines of Mexico may be found in Minerals Yearbook, 1941, as abstracted from the November 20, 1941, issue of Mineral Trade Notes, published by the

Bureau of Mines.

The decreased production and exports during the latter part of 1942 are partly attributable to the change in operating methods at the Lejocotes mines of the Compañia Minera de Oaxaca, near Tlaxiaco, Oaxaca. The conversion from underground to open-pit mining, accomplished with the financial aid of the Board of Economic Warfare, should be completed early in 1943. As a result, output in 1943 is expected to increase.

Morocco.—The annual production of antimony for both Algeria and Morocco totals less than 1,000 tons. Production figures for the

first 4 months of 1942 list 131 tons of 60-percent concentrates for Morocco. Stocks on May 1, 1942, were 715 tons. The ore is an antimony-lead sulfide occurring in veins in Carboniferous schists. The small reserves are being worked at Gouard ou Fellous and at Tafoudeit near Ouldjet in Soltane. For the past 10 years the annual production has ranged from 100 to 200 tons of antimony concentrates; however, potential production is estimated at 150 tons per month.

Peru.—Estimated production of antimony ores in Peru totaled 3,548 metric tons containing approximately 1,550 tons of antimony in 1942 as compared with 2,813 tons containing 1,565 tons of metal in 1941. Exports from Peru in 1942 totaled 2,557 metric tons of ore and concentrates, containing 1,247 tons of antimony, and 6 tons of anti-

mony bars containing 90 to 95 percent metallic antimony.

Although antimony is produced chiefly by the Cerro de Pasco Copper Corporation, mining is done largely by small producers. There are about 70 small antimony mines in Peru, scattered throughout the Departments of Puno, Tima, La Libertad, Huánuco, Ancash, Junin, and Huancavelica. The deposits of the Puno district, which supply half of the total output of Peru, are reportedly large but are not fully developed and produce only part of their potential total. The antimony occurs as concentrations of stibnite in quartz veins traversing belts of slate and schist. The mines are generally worked without mechanical equipment by the most primitive methods.

The new Cerro de Pasco Copper Corporation plant for treating Cottrell dust began operations in a small way in August 1942. As certain metallurgical problems remained to be solved at that time, it was thought that several months would elapse before the plant

would be operating properly and at capacity.

Turkey.—Stibnite is mined in the Turhal region southwest of

Amasya.

In 1941, the last year for which figures are available, Turkish production of antimony totaled only 120 metric tons (antimony metal content), but as development of small mines progresses the annual output should increase. In 1940, 638 tons of antimony concentrates were produced, of which 395 tons were exported to France and 243 tons to Japan. Production of concentrates in 1939 totaled 1,300 tons.

# **CADMIUM**

By Allan F. Matthews

#### SUMMARY OUTLINE

	Page			Page
General statement	795 Cc	nsumption and u	ises	798
Salient statistics	795 St	ocks		799
Domestic production	795 Pr	ices		799
Foreign trade	797 W	orld aspects of ca-	dmium industry	800

# GENERAL STATEMENT

Cadmium was in strong demand during 1942 for the protective plating of armament parts and by the end of the year was considered the fifth most critical nonferrous metal. Primary production increased only 2 percent in 1942, but new recovery units were installed that will boost the 1943 output appreciably. Cadmium was placed under priority control by the Office of Production Management January 17, 1942 (Order M-65)—amended by the War Production Board June 24 to provide for direct Government allocation. A ceiling price on cadmium at 90 to 95 cents a pound was established by the Office of Price Administration January 19, 1942 (Schedule 71).

Salient statistics of the cadmium industry in the United States, 1938-42, in pounds

	1938	1939	1940	1941	1942
Production (primary) Imports (metal) Exports	4, 294, 400 22, 582	4, 790, 500 309, 874	6, 363, 600 27, 491 387, 118	7, 233, 500 147, 378 171, 858	7, 370, 969 53, 298 283, 630
Consumption Stocks (year-end)	2 4, 100, 000 (1)	<sup>2</sup> 5, 900, 000	6, 178, 000 2, 844, 200	7, 766, 000 2, 610, 643	7, 659, 000 2, 408, 992

<sup>&</sup>lt;sup>1</sup> Data not available.

東京の東京の大学の大学の大学

# DOMESTIC PRODUCTION

Primary cadmium production established a new record in 1942 as the result of a 2-percent increase over 1941. Producers' shipments also advanced, but imperceptibly. The geographic distribution of primary cadmium production, based upon location of plants that produced metal or compounds (not upon origin of cadmium-containing ores), was as follows in 1942: 70 percent from 4 plants in four Western States, 20 percent from 10 plants in seven Central States, and 10 percent from 8 plants in four Eastern States. Cadmium is obtained only as a byproduct in the recovery of the common nonferrous metals, particularly zinc. Cadmium output will be stepped up in 1943; according to an estimate by the Board of Economic Warfare, 31 percent will come from domestic zinc-lead concentrates, 19 percent from imported Mexican flue dust, and 50 percent from imported zinc concentrates.

<sup>3</sup> Apparent consumption.

# Cadmium produced and shipped in the United States, 1938-42, in pounds

	1938	1939	1940	1941	1942
Production: Primary: 1	•				
Metallic cadmium	4, 077, 961	4, 411, 530	6, 154, 200	6, 937, 931	7, 323, 346
Cadmium compounds (Cd content) 2	216, 400	3 379, 000	209, 400	295, 600	47, 623
Total primary production  Secondary (metal and Cd content of compounds) 24	4, 294, 400	<sup>3</sup> 4, 790, 500	6, 363, 600	7, 233, 500	7, 370, 969
	(5)	( <sup>3</sup> <sup>5</sup> )	227, 900	379, 500	316, 345
Shipments <sup>6</sup> by producers: Primary: Metallic cadmium Cadmium compounds (Cd content) <sup>2</sup>	2, 525, 666	5, 190, 273	6, 467, 260	7, 044, 417	7, 233, 043
	211, 000	3 401, 200	205, 900	265, 700	78, 059
Total primary shipments  Secondary (metal and Cd content of compounds) 2 4	2, 736, 700 ( <sup>5</sup> )	<sup>3</sup> 5, 591, 500 (3 5)	6, 673, 200 227, 200	7, 310, 100 376, 500	7, 311, 102 304, 894

Figures showing primary cadmium production for 1940-42 are strictly comparable. The data for 1938-39 are exactly comparable with 1940-42 as to totals, but in the former period the cadmium content of some compounds made from metal is included with the compounds and excluded from the metal.
 Excludes compounds made from metal.
 Some secondary compounds included with primary compounds; Bureau of Mines not at liberty to publish figures separately for primary cadmium compounds.
 Bureau of Mines not at liberty to publish figures separately for secondary cadmium compounds.
 Data not available.
 Figures for 1938-39 represent sales.

# The following companies produced primary cadmium metal in 1942.

가능하다 경기 얼마나 있는 그는 그들은 항문이다.	Location of plant
American Smelting & Refining Co.	Denver, Colo.
American Zinc Co. of Illinois	Fairmont City, Ill., and Dumas, Tex.
Anaconda Copper Mining Co	Great Fella Mont
Eagle-Picher Mining & Smelting	Unantitalis, Mont.
Co.	Henryetta, Okia.
Harshaw Chemical Co	Elvria Ohio
National Zinc Co	Bartlesville Okla
Neo-Metal & Chemical Corpora-	Whitestone N V
tion.	wintescone, iv. 1.
New Jersey Zinc Co	Palmerton Pa
St. Joseph Lead Co	Herculangum Mo and Iosophtown Da
Sherwin-Williams Co	Coffeyville Kens
Sullivan Mining Co	Wellers Lists
II o consistent Defection of Maria	Kenogg, Idano.
U. S. Smelting, Refining & Mining	Midvale, Utah.
Co.	
U. S. Steel Corporation	Donora Pa

Cadmium compounds are produced principally from metal, although some are made directly from primary residues and secondary materials. Total production of cadmium compounds (in terms of Čd content) decreased 48 percent from 1941 as a consequence of conservation measures.

Cadmium compounds produced in the United States, 1940-42, in pounds

	19	)40	19	941	1942		
Compound	Gross weight	Cd content	Gross weight	Cd content	Gross weight	Cd content	
Sulfide 1 Oxide 2 Nitrate Hydrate Chloride Carbonate Bromide Sulfate Iodide Acetate	2, 287, 608 318, 393 29, 594 3 19, 799 15, 475 14, 733 6, 289 4, 324 (3) 1, 103	759, 500 250, 800 10, 800 3 14, 100 7, 600 9, 600 2, 500 2, 200 (8)	3, 304, 478 410, 748 138, 951 42, 995 57, 828 36, 806 17, 041 6, 771 4, 047 1, 300	1, 141, 500 361, 300 50, 600 31, 500 30, 100 24, 100 7, 000 3, 400 1, 300 600	1, 001, 124 594, 018 9, 710 4 24, 207 15, 225 14, 012 (4) 5, 442 1, 201 948	300, 414 519, 586 3, 546 4 15, 821 7, 924 9, 076 (4) 2, 584 369 406	
Total production	2, 697, 318	1,057,600	4, 020, 965	1, 651, 400	1, 665, 887	859, 726	

# FOREIGN TRADE 1

Imports.—All the cadmium metal imported in 1942 came from Belgian Congo and was added to the Government stock pile held by the Metals Reserve Co. Domestic cadmium production is partly from imported flue dust which in 1942 contained 1,723,728 pounds of cadmium—all from Mexico—and in 1941 contained 2,321,426 pounds—1,984,698 from Mexico, 334,137 from South-West Africa, and 2,591 from the Union of South Africa.

Metallic cadmium imported for consumption in the United States, 1938-42

Country	19	38	1939		1940		1941		1942	
	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value
Belgian CongoBelgium	20.007	\$28, 815	107 454	\$84, 904	27, 491	60 500			53, 298	\$40, 363
Canada Germany	55	163	30, 068 50	14, 642 148		\$9,520	136, 280	\$139, 898		
Italy Netherlands Norway	2, 240	1,406	35, 304 38, 038 6, 720	12, 649						
Poland and Danzig United Kingdom	220	190					11, 098	12, 166		
	22, 582	30, 574	309, 874	130, 973	27, 491	9, 520	147, 378	152, 064	53, 298	40, 363

Exports.—Cadmium exports totaled 283,630 pounds (251,059)of metal and 32,571 in compounds) in 1942 compared with 171,858 pounds (65,851 of metal and 106,007 in compounds) in 1941 and 387,118 pounds (286,529 of metal and 100,589 in compounds) in 1940. These figures were compiled by the Bureau of Mines from exporters (except that the figure for compounds in 1942 was estimated from data for gross weight obtained from the Department of Commerce); corresponding data for previous years are not available. All but an insignificant quantity of the cadmium metal exported in 1942 went to Russia under Lend-Lease agreement.

Includes cadmium lithopone and cadmium sulfoselenide.
 In addition to quantities shown, cadmium oxide consumed in making other compounds shown was produced as follows: 1940, 33,186 pounds (Cd content, 28,700 pounds); 1941, 33,649 pounds (Cd content, 27,500 pounds); 1942, 38,721 pounds (Cd content, 33,881 pounds).
 Iodide included with hydrate to avoid disclosure of confidential figures.
 Bromide included with hydrate to avoid disclosure of confidential figures.

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports (unless otherwise indicated) compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

# CONSUMPTION AND USES

Consumption.—Domestic consumption of cadmium totaled 7,659,000 pounds in 1942 compared with 7,766,000 pounds in 1941, a 1-percent decline.

Estimated distribution, by uses, of cadmium consumed in the United States, 1940-42

	1	1940	19	141	1 1942 1	
Use	Pounds	Percent of total	Pounds	Percent of total	Pounds	Percent of total
Electroplating	3, 692, 000	59.8	4, 586, 000	59. 1	6, 661, 000	87.0
Bearing alloys	1, 300, 000	21.0	1, 504, 000	19.4	282, 000	3.7
Solders	73, 000	1.2	130,000	1.7	201,000	2.7
Copper alloys	204,000	3.3	80,000	1.0	47,000	.6
Zinc alloys	36,000	.6	54,000	.7	9,000	.1
Low-melting alloys	23, 000	.4	43,000	.6	32,000	.4
Type metal	3,000	(2)	3,000	(2)	1,000	(2)
Other alloys	15, 000	.2	41,000	.5	9,000	.1
Total metal and alloys	5, 346, 000	86. 5	6, 441, 000	83. 0	7, 242, 000	94.6
Paints and varnishes	288,000	4.7	392,000	5, 0	93,000	1.2
Ceramics	256, 000	4.2	389,000	5.0	231, 000	3.0
Printing inks	105,000	1.7	126,000	1.6	4,000	.i
Rubber	50,000	.8	100,000	1.3	2,000	(2)
Laboratory reagents	44,000	.7	68,000	.9	47,000	6
Leather	35,000	.6	75,000	1.0	1,000	(3)
Gas-detector paper		1	30,000	.4	35,000	.5
Photography	5,000	(2)	11,000	.1	3,000	(2)
Other pigments 3	49,000	.8	134, 000	1.7	1,000	(2)
Tetal pigments and					14713	
chemicals	832, 000	13. 5	1, 325, 000	17.0	417, 000	5.4
Total cadmium consumed	6, 178, 000	100.0	7, 766, 000	100.0	7, 659, 000	100.0
					100	

<sup>1</sup> Distribution based in part on data from War Production Board.

Less than 0.1 percent.
 Includes plastics, textiles, artists' colors, etc., and some unclassified.

Electroplating.—The most important use of cadmium in the United States is as a protective coating for steel. Of the cadmium consumed in electroplating in this country in 1942, according to the War Production Board, aircraft took 42 percent, ordnance 24 percent, communications 7 percent, automobiles and tanks 6 percent, ships 5 percent, and electrical equipment 3 percent. To relieve the cadmium shortage, many parts whose specifications formerly called for cadmium plating are now galvanized, but there is little agreement regard-

ing the extent to which zinc can be substituted for cadmium.

Alloys.—Certain bearings containing over 95 percent cadmium and small quantities of nickel, silver, and copper are made for heavy-duty applications. Of the cadmium bearings produced in 1942, according to the War Production Board, aircraft took 45 percent, automotive vehicles 31 percent, rolling mills 12 percent, ships 11 percent, and industrial motors and ordnance 1 percent. Solders made of cadmium and various proportions of silver, lead, and zinc are being used more widely and are helping to conserve tin supplies. The addition of about 1 percent cadmium to copper trolley wire improves strength and wear resistance without seriously reducing electrical conductivity. Low-melting alloys containing 4 to 25 percent cadmium are used as a filler in bending thin-walled tubing, as a material for making spotting fixtures and jigs, and as a constituent of fire-detector systems, sprinkler apparatus, and valve seats for high-pressure gas containers.

The second secon

Compounds.—Cadmium sulfide and cadmium sulfoselenide are standard agents for imparting bright resistant yellow and red colors, respectively, to paints, ceramics, inks, rubber, leather, and other Papers coated with cadmium sulfide act as mustard-gas Cadmium nitrate is used in white fluorescent lamp coatdetectors. ings; the oxide, hydrate, and chloride in electroplating solutions; the carbonate in ceramics; and the halides in photography.

Toxicology.—The causes, effects, and prevention of cadmium poisoning, based upon a study of the 345 cases reported to date, were sum-

marized by the Public Health Service.2

# STOCKS

Total stocks of cadmium in the United States declined 8 percent in 1942, owing to reducing of consumers' inventories. Stocks of metallic cadmium held by producers, distributors, and the Government increased 20, 60, and 76 percent, respectively.

Cadmium stocks at end of year, 1941-42, in pounds

				-		
		1941 1		1942		
	Metallic cadmium	Cadmium compounds (Cd content)	Total cadmium	Metallic cadmium	Cadmium compounds (Cd content)	Total cadmium
Producers	452, 004 53, 507 82, 258 1, 536, 000 114, 352	104, 339 146, 814 15, 369 106, 000	556, 343 200, 321 97, 627 1, 642, 000 114, 352	544, 301 11, 895 131, 443 1, 199, 000 200, 946	83, 360 126, 736 28, 311 83, 000	627, 661 138, 631 159, 754 1, 282, 000 200, 946
Total stocks	2, 238, 121	372, 522	2, 610, 643	2, 087, 585	321, 407	2, 408, 992

### PRICES

Cadmium metal was quoted at 90 cents a pound for sticks and 95 cents for anode shapes throughout 1942. This level was established in 1941 through agreement between producers and distributors and the Office of Price Administration and was made mandatory January 19, 1942 (Schedule 71). The order was modified to permit, after June 22 (Amendment 1), sales of metal in small containers (5 pounds or less) at October (1941) price levels and to allow adjustable pricing contracts after October 26 (Amendment 2). The Office of Price Administration fixed ceiling prices on partly used anodes at 94 cents a pound, cadmium oxide at 95 cents a pound, and cadmium scrap at 35 cents per pound of contained cadmium, effective October 21, 1942 (Order 6, Maximum Price Regulation 204). The maximum prices are f. o. b. plant of the Udylite Corporation, Detroit, Mich., which was appointed by the Government-owned Metals Reserve Co. as its agent to assist in the cadmium stock-piling program and in the redistribution of idle or frozen materials.

Shipments of metallic cadmium, as reported to the Bureau of Mines by primary producers, had an average value of 79 cents a pound in 1942 compared with 78 cents in 1941 and 70 cents in 1940. Producers' quotations, according to Metal and Mineral Markets, averaged 90 cents in 1942 compared with 88 cents in 1941 and 80 cents in 1940.

Comprises principally 6 largest dealers.
 Partly estimated. Includes some material in process. Excludes stocks of compounds held by pigment and chemical consumers.

<sup>&</sup>lt;sup>1</sup> United States Public Health Service, Cadmium Poisoning: Public Health Repts., vol. 57, No. 17, April 24, 1942, pp. 601-612; Reprint 2371, 12 pp.

Prices for compounds remained unchanged during 1942. Cadmium sulfide was quoted at \$1.10 a pound, cadmium lithopone yellow at 55 to 65 cents a pound, cadmium lithopone red at \$0.80 to \$1.25 a pound, and cadmium bromide at \$1.65 to \$1.91 a pound, according to Oil, Paint and Drug Reporter.

# WORLD ASPECTS OF CADMIUM INDUSTRY

The United Nations control over four-fifths of the world new supply of cadmium, but nevertheless there were dire shortages of the metal in the United States, Great Britain, and Russia during 1942. Germany got along with about 16 percent of the supply by confiscating stocks in conquered countries, restricting the use of cadmium to solders and and other alloys, and adopting widespread substitution of galvanizing for cadmium plating.

World production of cadmium, 1937-42, by countries, in kilograms
[Compiled by B. B. Waldbauer]

Country	1937	1938	1939	1940	1941	1942
Australia (Tasmania) Belgian Congo	210, 608	199, 326	175, 150	(1)	(1) 2 400	(1) 2 28, 000
Belgium	271,000	182,000	3 530, 800	(1)	(1)	(1)
Canada	338, 018	317, 122	426, 234	411, 917	567, 573	511, 907
France	99,000	116,000	(i)	(1)	(1)	(1)
Germany	355,000	432,000	(1)	(1)	(1)	(1)
Italy	90, 850	69,000	(1)	(1)	(1)	(1)
Japan	2 30,000	2 30, 000	(1)	(1)	(1)	(1)
Mexico	619, 792	762, 398	816, 584	815, 734	906, 577	854, 264
Norway	154, 192	207, 667	138,000	(1)	(1)	(1)
Peru						2 2,000
Poland	124, 461	182, 591	(1)	(1)	(1)	(1)
South-West Africa 4	132, 763	259, 133	82, 155	39, 634	5 179, 497	(1)
U. S. S. RUnited Kingdom	<sup>2</sup> 50, 000	<sup>2</sup> 50, 000	(1)	(1)	(1)	(1)
	124, 142	124, 898	(1)	(1)	(1)	(1)
United States:		1	L		1. A.L.	
Metallic cadmium	1, 935, 003	1,849,722				3, 321, 797
Cadmium compounds (Cd content)	190,000	98, 200	171,900	95,000	134,000	21,600
	3, 972, 300	<del></del>		<del>                                     </del>	(1)	(1)

Data not available.
 Cadmium content of flue dust exported for treatment elsewhere; represents in part shipments from stocks on hand. To avoid duplication of figures, the data are not included in the total.
 Figures cover January to June, inclusive.

Belgian Congo.—Production of cadmium was begun in November 1941 by Union Minière du Haut Katanga as a byproduct of the preliminary roasting of zinc concentrates from the Prince Leopold mine to obtain sulfuric acid. The metal was exported to the United States.

Canada.—The Dominion of Canada produces five or six times its cadmium requirements, and the surplus is exported to the United Kingdom.<sup>3</sup> The Consolidated Mining & Smelting Co. of Canada, Ltd., Trail, British Columbia, and Hudson Bay Mining & Smelting Co., Flin Flon, Manitoba, are the two producers. The output of the latter company was increased in 1942, partly from a 10-ton pilot plant treating stock-piled zinc-copper-cadmium residues. Canadian cadmium consumption in 1940 was 142,019 pounds (64,419 kilograms), 85 percent of which was used in white-metal alloys. Primary cadmium may be bought and sold only under permit from the Metals Controller, according to an order effective June 1, 1942. Metallic cadmium was quoted at \$1.30 a pound throughout 1942 by Canadian Metals and Metallurgical Industries.

<sup>&</sup>lt;sup>3</sup> Northern Miner, vol. 28, No. 21, August 13, 1942, p. 14. <sup>4</sup> Graham, G. T. E., The Removal of Copper and Cadmium in the Hydrometallurgy of Zine: Canadian Jour. Research, vol. 20, No. 6, sec. B. June 1942, pp. 93-102.

# PLATINUM AND ALLIED METALS

By H. W. Davis

#### SUMMARY OUTLINE

	Page		Page
Summary	801	Refined platinum metals—Continued.	
Salient statistics	801	Secondary metals recovered	
Crude platinum	802	Prices	804
Production	802	Properties and uses	
Purchases	803	Consumption	. 806
Prices	803	Stocks	807
Refined platinum metals	803	Foreign trade	807
New metals recovered	803	World production	809

# SUMMARY

The great demand for platinum metals in the military program made 1942 the most important year in the history of the industry. Despite the unprecedented demand, supplies of platinum, palladium, ruthenium, and osmium were ample for both war and nonwar purposes; and with the use of iridium and rhodium in jewelry and other articles of personal adornment prohibited, the supply of those metals was sufficient for war needs. More platinum metals were refined, imported, and consumed in the United States in 1942 than in any other year. Compared with 1941, new platinum metals refined in 1942 (400,327 ounces) gained 162 percent, imports (335,954 ounces) 8 percent, and consumption (as measured by domestic sales—375,812 ounces) 30 The electrical industry, which ranked third as a consumer of platinum metals in 1941, rose to first place in 1942; the chemical industry again was the second-largest consumer; and the jewelry industry, which in peacetime was the largest user of platinum metals, was third in 1942.

Salient statistics of platinum and allied metals in the United States, 1941-42, in troy

	1941	1942		1941	1942
Production: Crude platinum from placers.	26, 221	1 23, 213	Stocks in hands of refiners, importers, and dealers, Dec. 31:		
New metals:	2 98, 376	2 244, 226	Platinum Palladium Other	150, 887 138, 014 33, 942	160, 724 107, 383 35, 280
PalladiumOther	49, 812 4, 435	140, 262 15, 839		322, 843	303, 387
Secondary metals:	152, 623 37, 522	400, 327 56, 150	Imports for consumption: Platinum Palladium Other	254, 714 46, 099 9, 182	1 317, 198 1 9, 984 1 8, 778
Palladium Other	12, 630 1, 417	16, 416 4, 045		309, 995	1 335, 954
	51, 569	76, 611	Exports: Ore and concentrates	244	159
			Refined metals and alloys, in- cluding scrap	15, 405	102, 46
			jewelry)	3, 204	1, 24

京本人のことには、おいとので、一般できたなないというか、一次一下の

<sup>&</sup>lt;sup>1</sup> Subject to revision.
<sup>2</sup> In 1942 includes 25,403 ounces (17,027 in 1941) of new platinum from domestic sources, comprising 21,063 ounces (5,219 in 1941) derived from crude placer platium, 7 ounces (3 in 1941) from ore, and 4,333 ounces (1,805 in 1941) obtained from domestic gold and copper ores as a byproduct of refining.

Despite the greatly increased demand for platinum metals in 1942,

prices remained level.

The use of rhodium in the manufacture of jewelry was prohibited by the War Production Board under Conservation Order M-95, effective March 11, 1942. This order was amended on April 1, 1942, to prohibit the use of rhodium alloys, as well as rhodium plating, in the manufacture of jewelry and other articles of personal adornment. Order M-162, as amended and effective October 31, 1942, prohibited the use of platinum and platinum alloys in the manufacture of jewelry.

Figure 1 shows graphically the trend in world production of plati-

num metals from 1914 to 1942.




FIGURE 1.—Trend in world production of platinum metals, 1914-42.

# CRUDE PLATINUM

Production.—Mine returns for 1942 indicate a production of 22,000 ounces of crude platinum (containing 19,360 ounces of platinum-group metals valued at \$1,010,000) in Alaska, 1,200 ounces in California, and 13 ounces in Oregon—a total of 23,213 ounces; comparable

<sup>&</sup>lt;sup>1</sup> Figures and other information for Alaska from Geol. Survey, U. S. Dept. of Interior. Figures for 1942 subject to revision.

figures for 1941 are 24,800 ounces of crude platinum (containing 21,555 ounces of platinum-group metals valued at \$1,078,000) in Alaska, 1,300 ounces in California, 41 ounces in Montana, and 80 ounces in Oregon—a total of 26,221 ounces. Production in Alaska came mainly from placer deposits in the Goodnews district of southwestern Alaska; most of it was mined by a large modern dredge and by well-mechanized draglines. In California most of the output of platinum was a byproduct of dredges working gold placers in Butte, Calaveras, Eldorado, Humboldt, Merced, Placer, Sacramento, San Joaquin, Siskiyou, Stanislaus, Trinity, and Yuba Counties. Production in Oregon came from Grant County.

Many gold and copper ores in the United States contain small quantities of platinum metals. In 1942, 9,805 ounces of platinum metals were recovered as a byproduct of refining gold and copper

ores, compared with 6,494 ounces in 1941.

Purchases.—Buyers in the United States reported purchases of domestic crude platinum from the following sources in 1942: Alaska, 22,142 ounces; California, 961 ounces; Montana, 2 ounces; and Oregon, 42 ounces—a total of 23,147 ounces (27,017 ounces in 1941). Domestic buyers also reported purchases of 53,661 ounces (38,124 ounces in 1941) of foreign crude platinum or osmiridium in 1942—157 ounces from Australia, 1 ounce from Canada, 53,353 ounces from Colombia, 30 ounces from the Philippine Islands, and 120 ounces from the Union of South Africa.

Prices.—Buyers reported purchases at \$28.79 to \$75.38 an ounce for domestic crude platinum and \$24.05 to \$97.55 an ounce for foreign crude platinum or osmiridium in 1942.

# REFINED PLATINUM METALS

New metals recovered.—Reports from refiners of crude platinum, gold bullion, nickel, and copper indicate that 400,327 ounces (a new record) of platinum metals were recovered in the United States from such sources in 1942, an increase of 162 percent over 1941. Of the new metals recovered in 1942, 91 percent was chiefly from concentrates from Canada and crude from Colombia, 6 percent was from domestic crude (chiefly from Alaska), and 3 percent was a byproduct of domestic gold and copper ores.

New platinum metals recovered by refiners in the United States in 1942, by sources, in troy ounces

	Platinum	Palladi- um	Iridium	Osmium	Rhodium	Ruthe- nium	Total
Domestic from— Crude platinum	21, 063	11 17	3, 329	786	28	55	25, 272 26
Gold and copper refining	4, 333	5, 432	35	5			9, 805
	25, 403	5, 460	3, 366	791	28	55	35, 103
Foreign from— Crude platinum Nickel and copper refining	42, 581 176, 242	246 134, 556	221 1, 515	98	5, 962	25 3, 737	43, 212 322, 012
	218, 823	134, 802	1, 736	98	6,003	3, 762	365, 224
Total recovery	244, 226	<b>140, 262</b>	5, 102	889	6, 031	3, 817	400, 327

New	platinum	metals	recovered	by	refiners in	the	United	States,	1938-42,	in	troy
					ounces						

Year	Platinum	Palladium	Iridium	Others	Total
1938	30, 444	3, 653	1, 247	869	36, 213
1939	36, 033	3, 491	1, 051	866	41, 441
1940	38, 951	4, 564	1, 517	2, 307	47, 339
1941	98, 376	49, 812	1, 392	3, 043	152, 623
1942	244, 226	140, 262	5, 102	10, 737	400, 327

Secondary metals recovered.—In 1942, 76,611 ounces of secondary platinum metals were recovered from the treatment of scrap metal, sweeps, and other waste products of manufacture that contain platinum metals, a 49-percent increase over 1941.

Secondary platinum metals recovered in the United States, 1938-42, in troy ounces

Year	Platinum	Palladium	Iridium	Others	Total
1938	44, 654	13, 489	1, 253	4, 895	64, 291
	45, 432	13, 039	2, 767	2, 205	63, 443
	47, 657	14, 773	1, 365	2, 635	66, 430
	37, 522	12, 630	659	758	51, 569
	56, 150	16, 416	1, 552	2, 493	76, 611

Prices.—Quotations <sup>2</sup> on platinum metals remained level during 1942. Platinum was quoted at \$36 an ounce, palladium \$24, iridium \$160 to \$175, osmium \$45 to \$48, rhodium \$125, and ruthenium \$35 to \$40. The quotations on palladium, rhodium, and ruthenium have prevailed for several years.

Properties and uses.—An excellent description of the properties and applications of the platinum metals, with particular reference to the war, has been presented by Wise,<sup>3</sup> from which the following has been drawn.

The chemical applications of the platinum metals, which rank high in immediate importance, are largely a consequence of their catalytic activity, resistance to corrosion, and resistance to oxidation at high temperatures, together with resistance to molten oxides and Of the catalytic uses, the production of nitric acid by the oxidation of a mixture of synthetic ammonia and air by passing it through a red-hot rhodium-platinum alloy gauze ranks first in wartime importance. The present demand for explosives naturally has led to a large expansion in output of nitric acid, which is used also in production of fertilizers, dyestuffs, photographic materials, plastics, and lacquer, and other chemical and metallurgical processes. inum is also used as a catalyst in the manufacture of sulfuric acid by oxidation of sulfur dioxide to sulfur trioxide. Palladium and platinum are excellent catalysts for hydrogenation as well as dehydrogenation. These metals are widely used in the laboratory and are being applied to larger-scale production in the manufacture of various special organic products, including vitamin adjuncts. Ruthenium also has been employed for certain rather special reactions in connection with the synthesis of long-chain hydrocarbons, and osmium tetroxide is an effective hydroxylation catalyst. Palladium has been utilized in supplying extremely pure hydrogen for furnace atmospheres.

<sup>&</sup>lt;sup>3</sup> E & MJ Metal and Mineral Markets, vol. 13, 1942. <sup>3</sup> Wise, E. M., Platinum at Work in 1942: Min. and Met., vol. 23, No. 428, August 1942, pp. 421–425.

Pure platinum is universally used as the anode in producing persulfuric acid, and hence hydrogen peroxide, and appears to be the most satisfactory for producing a variety of "per" salts and other highly oxidized materials. Platinum and iridium-platinum also are suitable for insoluble anodes in various electroplating and allied processes, including the recovery of metals from waste solutions. Platinum rupture disks are employed for safe handling of corrosive liquids and gases. Chemical laboratories have long used platinum for crucibles, electrodes, and other equipment, and with the use of microchemical technique many new pieces of platinum equipment have come into production. Use of platinum in plant-scale equipment has awaited the availability of platinum-clad sheets, pipe, rod, and lined reaction vessels, which can now be had in almost any desired size. One of the spectacular recent achievements in the ancient glass industry is the commercial production of fiber glass, which has provided a new and vastly superior insulation for copper wire, a chemically inert fabric, an excellent air-filter medium, and an improved storage-battery separator, as well as a versatile heat-insulation medium. Platinum, because of its resistance to attack by molten glass, made this possible, as the fiber is produced by permitting molten glass to pass through a bank of platinum nozzles from which it emerges in fine streams, which are stretched to produce the minute fibers required. The rayon industry utilizes platinum-gold and rhodium-platinum alloys in a somewhat similar way, as the viscose is forced through small

spinnerets made of one of these alloys.

The numerous electrical applications of platinum, palladium, and the other platinum-group metals are based upon their resistance to tarnishing by oxidation or sulfidation, resistance to spark erosion, high melting temperatures, and good mechanical properties. Certain special applications also depend on their resistance vs. temperature relationships or on definite thermoelectric properties. Palladium is used most extensively in the contacts of telephone relays. Platinum, either pure or hardened with up to 10 percent ruthenium or 25 percent iridium, is employed for contacts in voltage regulators, thermostats, and relays, and the two alloys are used for contacts in high-tension magnetos, which are of particular importance in aircraft. Spark plugs equipped with small-diameter platinum-alloy electrodes have found extensive use in the present war owing to their long life and resistance The ability to produce platinum wire as small as 40millionths inch in diameter and its immunity to oxidation have made possible electrical fuses that will blow at a few thousandths of an Fuses of a different type, also using platinum and palladium alloys, are employed to detonate explosives. Platinum is also employed in resistance thermometers, in temperature-compensating networks of electrical instruments, and in electrical gas analyzers, and rhodium-platinum alloy is the standard high-temperature precision Some of the hard platinum alloys, somewhat similar thermocouple. to those used for tipping fountain pens, are used for special electrical contacts and for bearings in small instruments and magnetic compasses; and some related alloys are used for long-life needles for phonographs. The highly reflective rhodium has proved most satisfactory for surfacing the great searchlight reflectors that have become so important in the war.

Both palladium and platinum are used extensively in dental metallurgy in gold dental alloys to impart superior tarnish resistance,

strength, and response to age-hardening treatment. Platinum-base alloys are used in both wrought and cast form for dental restorations of the highest type; palladium-gold alloys are employed for producing the porcelain-to-metal junction in most artificial teeth; and soft platinum-foil matrices are used for producing porcelain crowns and

inlays.

In the jewelry and decorative arts platinum is recognized as the ideal metal, particularly for gem-set jewelry. Ruthenium-palladium-is now finding much broader application in jewelry. Iridium was formerly the favorite hardener for jewelry platinum but has been supplanted by ruthenium to conserve iridium for war requirements. Both platinum and palladium are beaten into foil in the same manner as gold and are used for about the same purposes.

Consumption.—As pure metals, combined, clad, or alloyed with other metals, the platinum metals are employed in jewelry and dentistry, in the chemical and electrical industries, and for numerous miscellaneous purposes. Sales to consumers in the United States were 375,812 ounces in 1942, compared with 288,397 ounces in 1941.

The most widely used metal of the group is platinum, which constituted 269,176 ounces (71 percent) of the total platinum metals reported sold to consumers in the United States in 1942. The chemical industry, which advanced to first place as a consumer of platinum in 1941, maintained its rank in 1942, accounting for 35 percent (94,025 ounces) of the total sales. The largest outlet for platinum in the chemical industry in 1942 was as a catalyst to produce nitric and sulfuric acids. Important quantities were used also in laboratory ware, rayon spinnerets, and fiber glass. The electrical industry, which ranked third as a consumer of platinum in 1941, was a close second in 1942, taking 34 percent (92,961 ounces) of the total platinum The largest use for platinum in the electrical industry in 1942 was as magneto and other contacts. Sales of platinum to the electrical industry were 228 percent greater than in 1941. The jewelry industry, which dropped to second place in 1941, fell to third place in 1942, taking 25 percent (66,518 ounces) of the total platinum sales. Despite the ban on the use of platinum in jewelry during the last 2 months of 1942, sales were about the same as in 1941. The dental industry purchased 5 percent (13,077 ounces) and miscellaneous uses accounted for the remainder (1 percent, or 2,595 ounces) of the platinum sold in 1942.

Next to platinum, palladium is the most extensively used metal of the group; it constituted 81,460 ounces (22 percent) of the total platinum metals sold to domestic consumers in 1942. The electrical industry was the chief consumer of palladium in 1942, buying 35 percent (28,452 ounces) of the total sold. However, sales of palladium to the electrical industry were 20 percent less than in 1941. A close second in magnitude of consumption of palladium in 1942 was the dental industry (34 percent, or 27,480 ounces), which was followed by the jewelry industry (24 percent, or 19,658 ounces). Sales of palladium to the dental industry declined 13 percent in 1942, but those to jewelers increased 146 percent. Comparatively small quantities were sold for use in the manufacture of chemical ware (5,480 ounces) and

for miscellaneous purposes (390 ounces) in 1942.

The consumption of the other platinum metals—iridium, rhodium, osmium, and ruthenium—is comparatively small; it made up 7 percent (25,176 ounces) of the total for the group in 1942. Rhodium and ruthenium (in almost equal quantities) were the most extensively used metals of this group, followed in order by iridium and osmium.

The following table shows sales of platinum metals by refiners, importers, and dealers to consumers in the United States in 1942.

Platinum metals sold to consuming industries in the United States in 1942, in troy ounces

Industry	Platinum	Palladium	Iridium, osmium, rhodium, and ruthe- nium	Total
Chemical	94, 025 92, 961 13, 077 66, 518 2, 595	5, 480 28, 452 27, 480 19, 658 390	5, 668 12, 446 106 4, 275 2, 681	105, 173 133, 859 40, 663 90, 451 5, 666
	269, 176	81, 460	25, 176	375, 812

Stocks.—Stocks of platinum metals in the hands of refiners, importers, and dealers were 303,387 ounces on December 31, 1942, compared with 322,843 ounces at the close of 1941.

Stocks of platinum metals held by refiners 1 in the United States, December 31, 1938-42, in troy ounces

Year	Platinum	Palladium	Iridium	Osmium, rhodium, and ruthenium	Total
1938	71, 058 71, 393 144, 302 150, 887 160, 724	30, 071 29, 273 93, 244 138, 014 107, 383	33,	9, 631 9, 884 368 942 280	117, 911 117, 550 269, 914 322, 843 303, 387

<sup>&</sup>lt;sup>1</sup> In 1940 figures also include stocks held in the United States by importers from the United Kingdom; in 1941 and 1942 figures also include stocks held in the United States by all importers and dealers.

# FOREIGN TRADE 4

Imports.—Imports of platinum metals into the United States in 1942 established a new record and amounted to 335,954 ounces,5 a gain of 8 percent over the previous peak year 1941. The principal sources of imported platinum metals in 1942 were Canada (222,685 ounces), 5 Colombia (46,714 ounces), United Kingdom (33,576 ounces), and U.S.S.R. (32,226 ounces). Imports of unrefined platinum (excluding scrap) increased in 1942 to 271,023 ounces (226,951 in 1941), and imports of refined platinum (including scrap) to 46,172 ounces (27,763 in 1941). Imports of refined palladium dropped in 1942 to 9,984 ounces (46,099 in 1941). Imports of refined iridium, osmium, and ruthenium also declined substantially in 1942, whereas there was a marked gain in imports of refined rhodium. Figures on imports in 1942 are subject to revision.

Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the

<sup>&</sup>lt;sup>4</sup> Figures on imports and exports compared by Mr. B. Fine, of the Button of, the Department of Commerce.

The concentrates and residues imported from Canada contain, in addition to platinum, substantial quantities of palladium, iridium, rhodium, and ruthenium, but apparently only the platinum content is recorded by the Department of Commerce.

# Platinum metals imported for consumption in the United States, 1938-42

Year	Troyounces	Value	-Year	Troyounces	Value
1938	161, 189 306, 627 1 195, 645	\$4, 366, 912 9, 881, 531 1 5, 748, 005	1941 1942 <sup>3</sup>	1 309, 995 1 335, 954	1 \$7, 143, 612 1 8, 646, 635

<sup>&</sup>lt;sup>1</sup> The concentrates and residues imported from Canada contain also substantial quantities of palladium, ridium, rhodium, and ruthenium, but apparently only the platinum content is recorded by the Department of Commerce. <sup>2</sup> Subject to revision.

Platinum metals (unmanufactured) imported for consumption in the United States, 1941-42, by metals

	1	941	19	42 I
Metal	Troy ounces	Value	Troy ounces	Value
Platinum:  Ores and concentrates of platinum metals (platinum <sup>3</sup> content).  Grain and nuggets (including crude, dust, and residues) (platinum <sup>3</sup> content).  Sponge and scrap (platinum content).  Ingots, bars, sheets, or plates not less than ½-inch thick (platinum content).	175, 810 51, 141 17, 898 9, 865	\$3, 317, 809 1, 300, 601 635, 062 322, 989	202, 836 68, 187 13, 918 32, 254	\$4, 300, 690 2, 006, 500 341, 310 1, 193, 183
iridium Osmiridium Osmium Palladium Rhodium Ruthenium	254, 714 1, 292 266 1, 689 46, 099 2, 780 3, 155	5, 576, 461 279, 455 23, 851 58, 028 851, 174 271, 809 82, 834	317, 195 485 276 475 9, 984 4, 609 2, 930	7, 841, 689 63, 524 23, 367 20, 764 190, 899 430, 054 76, 349
	309, 995	7, 143, 612	335, 954	8, 646, 63

<sup>&</sup>lt;sup>1</sup> Subject to revision.
<sup>2</sup> The concentrates and residues imported from Canada contain also substantial quantities of palladium, rindium, rhodium, and ruthenium, but apparently only the platinum content is recorded by the Department of Commerce.

Platinum metals (unmanufactured) imported for consumption in the United States in 1942, by countries, in troy ounces 1

· <del>december 1</del>		Plati	num						
Country	Ores and concentrates of platinum metals (platinum scontent)	Grain and nuggets (including crude, dust, and residues) (platinum 2 content)	and scrap (plati-	Ingots, bars, sheets, or plates not less than 1%-inch thick (platinum content)	Iridium	Osmi- um and osmi- ridium	Palla- dium	Rhodi- um and ruthe- nium	Total
Canada Colombia United Kingdom U. S. S. R.	185, 913	20, 175 46, 711 1, 295	13, 838 3 4 73	32, 226 12	(3) 485 (3)	41 555 155	9, 484 498	2. 700 4, 830 9	222, 685 46, 714 33, 576 32, 226 753
	202, 836	68. 187	13, 918	32, 254	485	751	9, 984	7, 539	335, 954

<sup>&</sup>lt;sup>1</sup> Subject to revision.

<sup>2</sup> The concentrates and residues imported from Canada contain also considerable quantities of palladium, iridium, rhodium, and ruthenium, but apparently only the platinum content is recorded by the Department of Commerce.

<sup>3</sup> Less than 1 ounce,

Exports.—Exports of refined platinum metals and alloys (including scrap) increased to 102,460 ounces in 1942 from 15,405 ounces in 1941. However, the 1942 exports included 97,800 ounces of refined palladium, which was shipped to Canada for storage. On the other hand, the 1941 figures included 8,100 ounces of refined platinum which was reexported to U. S. S. R. Deducting these items, exports of unmanufactured platinum metals in 1942 and 1941 were 4,660 and 7,305 ounces, respectively. Canada and Argentina were the chief foreign markets for platinum metals in 1942.

Platinum and allied metals exported from the United States, 1938-42

Year	Ore and tra		gots, s	n (bars, in- heets, wire, , and other including	iridium ium, and osi	ruthenium, nium (met- alloys, in-	Manufactures of, except jewelry		
	Troy ounces	Value	Troy ounces	Value	Troy ounces	Value	Troy ounces	Value	
1938	(1) (1) (1) (244 159	(1) (1) (1) (1) \$11, 713 6, 581	2 33, 635 2 46, 329 2 55, 027 2 15, 405 3, 354	2\$1, 156, 644 2 1, 528, 563 2 2, 280, 339 2 607, 333 126, 007	(2) (2) (2) (2) (2) (2) 99, 106	(2) (2) (2) (2) (2) \$2, 301, 953	796 4,041 1,800 3,204 1,246	\$31, 111 213, 445 96, 703 160, 674 61, 088	

Not separately classified.
 Palladium, rhodium, iridium, osmiridium, ruthenium, and osmium included with platinum; not separately classified before 1942.

Platinum and allied metals exported from the United States in 1942, by countries

Country	Ore and tra	concen- tes	gots, sl	to (bars, in- neets, wire, and other including	iridium ium, and osı	n, rhodium, n, osmirid- ruthenium, nium (met- alloys, in- scrap)	Manufactures of, except jewelry	
	Troy ounces	Value	Troy ounces	Value	Troy ounces	Value	Troy ounces	Value
Argentina Brazil Canada Chile Netherlands In-	46	\$1, 573	251 290 1, 733 234	\$9, 991 10, 884 73, 148 9, 291	462 93 98, 376 57	\$13, 728 2, 912 2, 279, 737 2, 648	78 75 640 39	\$5, 107 7, 192 24, 147 2, 087
diesOther countries	113	5, 008	321 525	11, 413 11, 280	118	2, 928	2 412	79 22, 476
	159	6, 581	3, 354	126, 007	99, 106	2, 301, 953	1, 246	61, 088

## WORLD PRODUCTION

Because of restriction on the publication of statistics by certain governments, figures for many countries since 1939 have not been available.

Canada.—According to the Dominion Bureau of Statistics, recoveries of platinum metals from the nickel-copper ores of the Sudbury district, Ontario, were 298,400 ounces of platinum and 226,600 ounces of other platinum-group metals in 1942 (an all-time high), compared with 124,257 ounces of platinum and 97,432 ounces of other platinum-group metals in 1941. Placers in British Columbia yielded 30 ounces of platinum in 1942, compared with 60 ounces in 1941.

Colombia. - Colombia exported 49,163 ounces of crude platinum in 1942 (37,349 in 1941). The South American Gold & Platinum Co. produced 25,786 ounces of crude platinum metals in 1942 (30,548 in 1941) and 51,974 ounces of gold (72,582 in 1941). The figures for other operators are not available.

Union of South Africa. Figures on output of platinum metals are not available for all of 1942, but it is reported that production to the full capacity of the plant proceeded uninterruptedly during the year.

The output was shipped to England for refining.

World production of platinum and allied metals, 1937-42, in troy ounces [Compiled by B. B. Waldbauer]

Country and product	1937	1938	1939	1940	1941	1942
Australia:		and the				
New South Wales: Placer platinum	46	8	(1)	(1)	(1)	(1)
Tasmania: Placer osmiridium	586	191	283	(1)	(1)	(1)
Belgian Congo: From refineries:	000	101	200	(3)	(5)	(-)
Palladium	12,507	1,575	3, 312	(1)	(1)	(1)
Palladium Platinum	2, 122	225	868	(1)	(1)	(1)
		220	300	(-)	(-)	(-)
	22	16	25	24	60	30
From refineries: 1	22	10	20	24	00	00
Placer platinum From refineries: 2 Platinum Other platinum metals	139, 355	161, 310	148, 877	108, 464	124, 257	298, 400
Other platinum metals	110,000	130, 893	135, 402	91, 522	97, 432	226, 600
Colombia: Placer platinum (exports)	29, 315	34, 549	39, 070	35, 859	37, 349	49, 163
Ethionia. Placer platinum (experts)	3, 376	3, 537			(1)	(1)
Ethiopia: Placer platinum taly: From refineries: Platinum	1, 286	1,029	(1)	(1)		
apan: Placer platinum			(1)	(1)	(1)	(1)
Netherlands Indies (probably placer plat-	(1)	(1)	(-)	(-)	(-)	(9)
inum)		21	28	34	(0)	(1)
New Zealand: Placer platinum	55	1	13	34	(1) 35	(1)
Panama: Placer platinum	267	1	13			
Panya . 2					(1)	(1)
Placer platinum	20	41	2	(1)	(1)	(1)
Placer osmiridium	20	41		(1)	1 23	(1)
lierra Leone: Placer platinum	308	180	83	(1)	(1) (1) (1)	(1)
Union of South Africa:	308	180	83	135	(1)	(4)
Platinum (content of platinum metals)	17 770	10 000	10 000	90 140	8 14 90F	8 10 00
Concentrates (content of platinum met-	17, 776	18, 256	18,068	20, 140	5 14, 205	6 16, 865
	01 040	95 194	41 040	F1 00F	5 74 700	8 49 99
Osmiridium 7	21,849	35, 124	41, 243	51, 835	\$ 54,790	6 43, 825
Osmiridium 7 J. S. S. R.: Placer platinum 8	5,790	5, 354	7,031	(1)	100,000	(1)
	100,000	100,000	100,000	100,000	100,000	100,000
Placer platinum	10 000	40.000	00 400	00 000	00 001	0.00.010
Ore (content of platforms and tall)	10, 803	40, 932	32, 460	33, 800	26, 221	23, 213
Ore (content of platinum metals)  From refineries: 10	124	90	66		15	26
	4 70	0.70	F 070	4 450	1 00-	4 000
Platinum.	4,761	3,761		4, 470	1,805	4, 333
Other platinum metals	5, 817	3, 486	3, 364	3, 304	4, 689	5, 472
	11 476, 000	11 541, 000	11 540, 000	11 465, 000	11 483, 000	11 790, 000

<sup>1</sup> Data not available.

<sup>&</sup>lt;sup>2</sup> Recovered from nickel-copper mattes. <sup>3</sup> Year ended June 30 of year stated.

Produced from platinum ores.
January to November, inclusive.
January to October, inclusive.
Produced from treatment of gold ores on the Rand.

<sup>8</sup> Estimated production.

Subject to revision.

New platinum metals recovered in gold and copper refining of domestic materials.

# **TITANIUM**

By Allan F. Matthews

# SUMMARY OUTLINE

	Page		Page
General statement	811	Consumption and uses	814
Government control	811	Prices	816
Domestic production	812	Technology	816
Foreign trade	813	World production	817
Stocks	814		

# GENERAL STATEMENT

The fading of summer in the Adirondack Mountains brought with it the first large-scale shipments of ilmenite from a mine near Tahawus, N. Y., which is to render the United States self-sufficient in ilmeniteprincipal ore of titanium. Domestic production of ilmenite tripled in 1942 compared with 1941, but rutile output was held somewhat below its normal level by a plant-expansion program at the Arkansas property. Mining of both titanium minerals is expected to increase greatly in 1943. Ilmenite imports, normally principally from India, slumped in 1942 to a fraction of their former volume, causing consumers to draw heavily on their stocks while awaiting domestic production to reach its stride. In contrast, rutile imports were able to increase in 1942 because of the smaller tonnages involved, a higher shipping priority rating, the relative proximity of Brazilian supplies, and the availability of cargo space on vessels returning from delivery of military supplies to Australia. White pigments and welding-rod coatings. took the bulk of the ilmenite and rutile, respectively, consumed in 1942, but both minerals also were consumed in ferrotitanium.

### GOVERNMENT CONTROL

Rutile was put under import control by the Office of Production Management, December 26, 1941 (Order M-63), and inventory restrictions on ilmenite were removed by the War Production Board, June 26, 1942 (Amendment 2, Order M-161). Producers of titanium pigments were directed to set aside a pool of 20 percent of their production for allocation by the Office of Production Management, effective December 1, 1941 (Order M-44). Subsequent amendments moved the effective date to January 1, 1942; clarified the original text; effective February 1 increased the allocation pool to 25 percent of the output; and December 9 revoked the entire order. Dealers were verbally requested by the War Production Board in the spring of 1942 to divert to welding-rod and alloy producers the quantities of rutile normally moving to ceramics manufacturers, although no formal order to that effect was promulgated.

Price action on titanium pigments first appeared January 3, 1942, when to stem a proposed advance the Office of Price Administration requested stabilization of prices at levels of October 1, 1941. The request was made mandatory March 1, 1942 (Price Schedule 98). Amendments allowed one producer to sell above the maximum price for 2 months, provided for additional means of enforcement, and after December 2 permitted adjustable pricing for long-term contracts.

# DOMESTIC PRODUCTION

Ilmenite production in the United States tripled in 1942 compared with 1941 and set a new record, but rutile output decreased 15 percent. The decline was due primarily to a stoppage of Arkansas production during plant enlargement. Ilmenite concentrates shipped in 1942 contained 42 to 52 percent TiO<sub>2</sub>, and rutile concentrates ranged from 90 to 94 percent TiO<sub>2</sub>. Production and shipments, 1939–42, are shown in the following table. The Bureau of Mines is not at liberty to publish corresponding figures for 1929–38.

Production and mine shipments of titanium concentrates from domestic ores in the United States, 1939-42

		Ilmenite		Rutile			
Year	Production	Shipr	nents	Production	Shipments		
	(short tons)	Short tons	Value 1	(short tons)	Short tons	Value	
1939 1940 1941 1942	14, 602 20, 668 23, 297 (2)	16, 872 20, 702 21, 526 (2)	\$137, 042 183, 686 196, 522 (2)	(2) 2, 888 3, 130 2, 648	(2) 2, 657 3, 431 2, 649	(2) \$393, 243 493, 782 410, 956	

Represents cost of production for some producers whose product is consumed by affiliated companies.
Bureau of Mines not at liberty to publish figures.

Arkansas.—The Titanium Corporation sold its rutile property at Malvern, Magnet Cove district, Hot Spring County, in March 1942 to the Titanium Alloy Co. of Arkansas, Inc., subsidiary of the Titanium Alloy Manufacturing Co. The property was inactive from January to September, during which time the concentrating plant was enlarged. In its decade (1932–42) of operation the Titanium Corporation produced 3,771 short tons of rutile averaging 93 percent TiO<sub>2</sub> and shipped 3,621 tons valued at \$440,758. In addition, it produced 1,281 tons of rutile averaging 52 percent TiO<sub>2</sub> and shipped 29 tons valued at \$583; the remainder was an inventory sold with the plant and will be brought up to commercial grade by the new operator.

Florida.—For 3 years the Riz Mineral Co. (formerly the Consolidated Operations Corporation) has been recovering rutile, ilmenite, and zircon from beach sands near Melbourne, Brevard County. Unworked since 1927, the beach deposits in Duval and St. Johns Counties near Jacksonville will yield large quantities of rutile in 1943, according to present plans of the Titanium Alloy Manufacturing Co.

New York.—The Sanford Lake titaniferous magnetite deposit near Tahawus, Essex County, was opened in 1942 by the Titanium Division of the National Lead Co., which granted a 25-percent interest in the

813 TITANIUM

The second of th

である。如果を見るとあるようなのでは、

project to the Krebs Pigment & Chemical Division, E. I. du Pont de Nemours & Co., Inc. The mine is known as the MacIntyre Development. Production began in August and by the end of the year was well on the way toward a daily output of 900 short tons of ilmenite concentrates (48 percent TiO2) and 1,800 tons of magnetite concentrates (64 percent Fe, low P, 9 percent TiO<sub>2</sub>, 0.35 percent V) derived from 4,500 tons of ore (16 percent TiO2). Treatment of the ilmenite involves grinding to pass a 20-mesh screen and concentration by wet and dry magnetic separators. Proved ore reserves total 15 million tons, and probable reserves of the district are prodigious.

North Carolina.—Ilmenite production was begun in January 1942 at Finley, Caldwell County, by the Yadkin Valley Ilmenite Co., subsidiary of the Glidden Co. The feasibility of producing ilmenite from black sands of Albemarle Sound was investigated by the North Carolina State Board of Conservation and Development and E. I. du Pont de Nemours & Co., Inc., Wilmington, Del., but results were not encouraging. A rutile deposit near Shooting Creek, Clay County, from which some shipments were made about 30 years ago, was under development in 1941 by the Southern Minerals Co., Asheville, but most of the property was condemned by the Tennessee Valley Authority for its Chatuge Dam project.

Virginia.—Rutile and ilmenite are produced near Roseland, Nelson County, by the American Rutile Corporation, subsidiary of the Metal & Thermit Corporation. Ilmenite is mined in the same district by the Southern Mineral Products Co., subsidiary of the Vanadium Corporation of America; this property is estimated to contain at least

4 million tons of titanium dioxide.2

# FOREIGN TRADE 3

Imports.—Ilmenite imports in 1942 comprised 4,540 short tons from Canada, 2,942 from Australia, 1,287 from Brazil, and 1,165 from India compared with 1941 entries of 156,079 tons from India, 5,725 from Canada, 4,093 4 from Australia, 3,709 from Brazil, and 969 from Portugal. Imports of rutile in 1942 comprised 4,967 short tons from Brazil, 4,661 from Australia, 111 from French Equatorial Africa, and 35 from French Cameroun compared with 1941 entries of 3.752 4 tons from Australia and 2,448 from Brazil. Australian concentrates classified as "Zirconium ore" by the Department of Commerce are about half zircon, and the remaining content is largely rutile and ilmenite with some gangue (magnetite, garnet, etc.); the rutile and ilmenite content of such concentrates is estimated and included in the preceding figures. After importation the mixed concentrates are separated into their component minerals by the International Titanium Corporation (subsidiary of the American Rutile Corporation and Ventures, Ltd.), Carteret, N. J.; Orefraction, Inc., Pittsburgh, Pa.; and Titanium Alloy Manufacturing Co., Niagara Falls, N. Y. There were no imports of ferrotitanium, 1941–42.

<sup>1</sup> Crockett, R. E., Eastern Magnetite: Min. and Met., vol. 24, No. 434, February 1943, p. 84.
Hagar, I. D., The MacIntyre Development—New Source of Titanium: Eng. and Min. Jour., vol. 143,
No. 12, December 1942, pp. 47-49.
Hagar, I. D., Ilmenite and Magnetite Produced in Quantity at National Lead's New MacIntyre Development: Min. and Met., vol. 23, No. 432, December 1942, pp. 594-596.
Mining and Contracting Review, MacIntyre Development—Historic Mine Reopened: Vol. 44, No. 13,
July 15, 1942, pp. 7 and 17.

Bevan, Arthur, Virginia's War Mineral Resources: Virginia Geol. Survey Reprint Series 4, 1942, p. 5.
Figures on imports and exports (unless otherwise indicated) compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.
Partly estimated. See accompanying table, footnote 2.

Titanium concentrates i imported for consumption in the United States, 1938-42

		Ilmenite	Rutile					
Year	Short tons		Value of "As	Short	Value of "As			
	As reported	Total 2	reported" 3	As reported	Total 2	reported" 3		
1938	234, 275 286, 576 221, 641 166, 846 7, 115	234, 141 287, 191 223, 891 170, 689 10, 369	\$1, 018, 403 1, 126, 200 750, 590 629, 940 56, 694	230 442 156 3, 114 6, 479	364 787 2, 164 6, 291 10, 465	\$26, 533 23, 170 14, 849 306, 176 626, 375		

of Commerce.

<sup>3</sup> Value pertains to "As reported" quantity only. Value of remainder included with "Zirconium ore." (See chapter of this volume on Minor Metals.)

Exports.—Exports in 1942 comprised 617 short tons (\$117,886) of titanium concentrates, 491 tons (\$61,909) of titanium ferro-alloys, 15 tons (\$9,938) of titanium tetrachloride, and 9 tons (\$3,728) of other titanium compounds.

# STOCKS

Stocks of ilmenite were cut in half during 1942 as a result of virtual cessation of imports from India and consequent necessity for consumers to draw heavily on inventories. On the other hand, imports of rutile from Australia and Brazil were not only maintained but appreciably augmented in 1942 so that, even in the face of greatly increased consumption, total inventories of rutile climbed 56 percent. Industry stocks of rutile actually declined 3 percent, but that trend was offset by the stock-piling program of Government-owned Metals Reserve Co.

Stocks of titanium concentrates in the United States at end of year, 1941-42, in short

		1941				1942			
Stocks	Ilm	enite	Rutile		Ilmenite .		Rutile		
	Gross weight	Estimated TiO <sub>2</sub> content	Gross weight	Estimated TiO <sub>2</sub> content	Gross weight	Estimated TiO <sub>2</sub> content	Gross weight	Estimated TiO <sub>2</sub> content	
Mine	28, 106 12, 867 311, 087	12, 087 6, 032 178, 258	75 2, 387 1, 144 31	53 2, 238 1, 072 29	11, 917 11, 541 149, 153	5, 142 5, 371 81, 735	75 1, 702 1, 707 2, 194	53 1, 588 1, 589 2, 062	
Total stocks	352, 060	196, 377	3, 637	3, 392	172, 611	92, 248	5, 678	5, 292	

<sup>&</sup>lt;sup>1</sup> Includes ilmenite and rutile content of mixed zirconium-titanium concentrates.

# CONSUMPTION AND USES

Consumption of ilmenite decreased 6 percent and that of rutile increased 67 percent in 1942 compared with 1941. Ilmenite was used

<sup>&</sup>lt;sup>1</sup> Classified as "Ore" by Department of Commerce.

<sup>2</sup> Includes Bureau of Mines estimate of ilmenite and rutile, respectively, contained in Australian zircon-rutile-ilmenite concentrates classified as "Zirconium ore" by Department of Commerce. Data for 1938 are adjusted to apportion Australian zircon-rutile-ilmenite concentrates classified as "Ilmenite" by Department

principally in pigments (95 percent) and alloys (5 percent) and rutile in welding-rod coatings (84 percent), alloys (15 percent), and ceramics (1 percent).

Consumption of ilmenite and rutile in the United States, 1941-42, in short tons

Product	Ilme	enite	Rutile		
	Gross weight	Estimated TiO <sub>2</sub> content	Gross weight	Estimated TiO <sub>2</sub> content	
Pigments (manufactured titanium di- oxide) <sup>1 2</sup> Welding-rod coatings <sup>1</sup> Alloys Ceramics Miscellaneous <sup>3</sup>	267, 944 58 7, 104	147, 905 30 3, 031	5, 461 709 172 19	5, 133 673 162 18	
Total consumption	275, 106	150, 966	6, 361	5, 986	
1942 Pigments (manufactured titanium dioxide) 12 Welding-rod coatings 1 Alloys Ceramics	244, 465 56 11, 802	134, 964 28 5, 899	8,857 1,652 92	8, 326 1, 526 86	
Miscellaneous 3	1, 212	521	15	14	
Total consumption	257, 535	141, 412	10, 616	9, 952	

<sup>1 &</sup>quot;Pigments" include all manufactured titanium dioxide, consumption of which in welding-rod coatings was 1,700 short tons in 1941 and 4,900 tons in 1942.

Titanium pigments.—Manufactured titanium dioxide obtained from ilmenite is used as a white pigment, principally in paint, varnish, and lacquer but also in paper, linoleum, rubber, coated textiles, leather, printing ink, soap, and cosmetics. Nonpigment applications of manufactured titanium dioxide include ceramics and welding-rod coatings. Domestic production of titanium pigments in 1942 receded from the high levels of 1941 at about the same rate as lead pigments and registered the second-best year to date. The output was double that of 1938 and was more in tonnage and twice as large in dollar volume as any other white pigment. Titanium white paints are noted for a high degree of opacity (covering power), reflectance (brightness), whiteness, and durability.

Welding-rod coatings.—Some 321,000 short tons of titanium-coated welding rods were produced in the United States in 1942 compared with 152,000 tons in 1941. According to Iron Age, the quantity of all types of welding rods produced in October 1942 was a little over 35,000 tons. Of this amount 60 to 70 percent was being used in shipbuilding to replace riveting with welding, thereby reducing steel requirements for cargo ships by 10 percent.<sup>5</sup> Titanium shields the arc from oxidation during welding and produces a brittle slag that protects the cooling weld deposit; it is usually added to coating compositions as rutile, manufactured titanium dioxide, or ilmenite.

Titanium alloys.—Ferrocarbontitanium (15–20 percent Ti, 3–8 percent C) is a powerful deoxidizer in steel melts, and ferrotitanium (18–45 percent Ti, 0.1 percent C max.) is added to steel to refine the grain, to

 <sup>2</sup> Partly estimated.
 3 Consists of ilmenite used as a steel flux and rutile used in lamp-electrode coatings and as a steel deoxidizer.

<sup>&</sup>lt;sup>5</sup> Oliver, Frank J., Welding—Given Tremendous Impetus by War: Iron Age, vol. 151, No. 1, January 7, 1943, p. 127.

inhibit intergranular corrosion of stainless steels, and to prevent airhardening of 5-percent chromium steels. Titanium is added to a number of nonferrous alloys, particularly to aluminum to increase strength and ductility, and is a constituent of a number of complex deoxidizers. The use of the pure metal is limited principally to radio tubes.

Other uses of titanium.—One hundred to two hundred short tons of ilmenite are consumed monthly by the Rustless Iron & Steel Corporation, Baltimore, Md., as a replacement for fluorspar (which, according to the company, emits fumes causing illness to workers) in making titanium-bearing stainless steel. Rutile and manufactured titanium dioxide are used in ceramics, principally to improve the acid resistance of porcelain enamels, to impart colors ranging from cream to brown in pottery bodies and glazes, and to make electric insulators. Consumption of rutile in ceramics was curtailed in 1942, and the quantities thus conserved were diverted to welding-rod coatings and alloys. Small quantities of rutile are used in lamp-electrode coatings of street lights and as a deoxidizer (with aluminum) in special alloy steels. Titanium carbide is a constituent of hard cutting alloys used in ma-Titanium tetrachloride is an important smoke-screen chine tools. chemical.

# PRICES

Titanium (in all forms) showed no price changes in 1942. Ilmenite, 60 percent TiO<sub>2</sub>, was nominally quoted at \$28-\$30 a long ton, f. o. b. Atlantic seaboard, according to Metal and Mineral Markets. One consumer was paying \$31.50 a ton for Indian material early in the year. Rutile, 94 percent TiO<sub>2</sub>, was listed at 8-10 cents a pound. Steel quoted ferrotitanium, ton lots, at \$1.23 per pound of contained Ti for 40- to 45-percent grade and \$1.35 for 20- to 25-percent grade; and ferrocarbontitanium, 15-20 percent Ti, at \$142.50 a short ton for 6-to 8-percent carbon and \$157.50 for 3- to 5-percent carbon. Titanium metal, 96-98 percent, was listed at \$5-\$5.50 a pound. The base price of manufactured titanium dioxide was fixed at 14½-16½ cents a pound by Office of Price Administration Schedule 98, noted under Government Control.

### TECHNOLOGY

Titaniferous magnetite analyzing 18 percent TiO<sub>2</sub>, from Poplar Lake, Minn., was crushed to minus-48-mesh and treated by hydraulic classification, tabling, and magnetic concentration to yield a product containing 43 percent TiO<sub>2</sub>. The effects of titanium in blast-furnace charges and the recovery of vanadium from Sanford Lake ilmenite tailings (titaniferous magnetite) were investigated by the Bureau of Mines, the University of Minnesota, and the National Lead Co. An improved method of making powdered titanium metal was patented.

<sup>&</sup>lt;sup>6</sup> Minnesota Geological Survey, Notes on Titanium and Vanadium (mimeographed): 1942, 4 pp.

<sup>†</sup> Wood, C. E., Joseph, T. L., and Cole, S. S., Smelting of Vanadium-Bearing Titaniferous Sinter in an Experimental Blast Furnace: Bureau of Mines Rept. of Investigations 3679, 1943, 24 pp.

<sup>†</sup> Comstock, George F., and Efimoff, Viatcheslav V. (to Titanium Alloy Manufacturing Co.), Powdered Titanium Metal: U. S. Patent 2,273,834, February 24, 1942.

中、大学、一次の大学の大学教教院、教育とないのである。 とうこうしょう

# WORLD PRODUCTION

The United Nations controlled most of the known commercial deposits of titanium in 1942. The Axis countries had access only to mines in Norway and Malaya, unless in addition neutral Portugal sold ore to the Nazis or collaborationist Vichy France contributed material from Senegal. Cameroun concentrates, under protection of the Fighting Free French, were shipped to Great Britain and the United States. Available data on world production of ilmenite and rutile in recent years are shown in the following table.

World production of titanium concentrates (ilmenite and rutile), 1937-42, by countries, in metric tons

[Compiled	by	В.	в.	Waldbauer]

Country	1937	1938	1939	1940	1941	1942
Ilmenite:						
Australia:		1 1 1				1000
New South Wales	681	(1)	742	2, 270	4,808	(1)
Queensland			1	-,0	254	à là
Brazil (exports)	234	317	10	12	4, 471	15
Canada	3, 836	188	3, 351	4, 114	11, 477	4, 768
Egypt	317	90	(1)	(1)	, 2	
Federated Malay States (exports)	6, 290	6, 462	11.098	2,596	(1)	(1) (1)
India, British	182, 142	256, 268	(1)	2 243, 850	(1)	(1)
Norway	84, 209	62,724	55,027	(1)	(1)	<sup>2</sup> 60, 000
Norway Portugal	1, 456	568	409	399	798	(1)
Senegal	3, 075	8, 436	(1)	5, 798	895	(1)
United States	(3)	(3)	13, 247	18, 750	21, 135	(3)
Rutile:		` ` `	77,77	- 500 C		1.5
Anstralia:						
New South Wales	4 1, 141	4 460	790	2,044	4, 440	(1)
Queensland					254	(1)
South Australia		8	2	2	(5)	(1)
Brazil (exports)	377	488	489	499	2, 369	4, 615
Cameroun (French)	103	118	6 159	(1)	(1)	(1)
Norway	187	124	166	(1)	(1)	(1)
South-West Africa	16			l`	(1)	(1)
United States	(3)	(3)	(3)	2,620	2, 839	`2, 402

Data not available.

Algeria.—The Keddaradans mine, Palestro district, produced 1,475 metric tons of titanium-zirconium concentrates in the first 4 months of 1942.

Australia.—Mixed rutile-ilmenite-zircon concentrates are produced in New South Wales by Porter & Derrick at Cudgen Headlands, by Metal Recoveries Pty., Ltd., at New Brighton, and by Zircon Rutile. Ltd., at Byron Bay; and in Queensland by Minerals Deposit Syndicate at Little Burleigh. Most of the concentrates are exported in mixed form to the United States; the output of the first-named company goes to the Titanium Alloy Manufacturing Co., of the second to International Titanium Corporation, and of the other two largely to Orefraction, Inc. A little rutile is also produced at Williamstown, South Australia. Some titanium concentrates are consumed in Australia by the Broken Hill Proprietary Co., Ltd., in making ferrotitanium.

Subject to revision.

<sup>4&</sup>lt;sup>3</sup> Bureau of Mines not at liberty to publish figures.
5 In addition, zircon-rutile-ilmenite concentrates were produced as follows—1937: 73 tons; 1938: 98 tons.

Less than 1 ton. Exports.

Brazil.—Production of rutile in Brazil in 1941 was estimated at 2,500 metric tons, principally from Goyaz, Ceara, and Minas Gerais. Concentrates average 70 to 95 percent TiO<sub>2</sub>, the higher grades bringing \$170 a ton, f. o. b. shipping port. Mining conditions were described. Cameroun (French).—Rutile exports from French Cameroun in

January 1940 were 51 metric tons.

Canada.—Ilmenite is produced at St. Urbain, Quebec. Following an announcement by the Quebec Bureau of Mines that field work indicated favorable opportunities for ilmenite in the Romaine River area, Saguenay County, 11 a massive deposit of ilmenite containing about 37 percent TiO2 and 53 percent FeO was discovered at Allard Lake, southwest of Havre-St. Pierre, by the Vital Metals Prospecting

Syndicate.12

India.—Sands of the Malabar coast, State of Travancore, have been the world's principal source of ilmenite; they also yield rutile, zircon, and monazite. Ilmenite production was about 5,100 metric tons in August 1942, compared with a monthly capacity of 32,000 tons, and stocks on hand were 93,400 tons—due primarily to unavailability of cargo space to the United States. There were no inventories of rutile at that time, and the monthly output of 230 metric tons was expected by March 1943 to reach 380 tons, most of which was under contract to the British Ministry of Supply. Ilmenite cost about \$5 a long ton, f. o. b. Cochin, but the freight rate to the United States was \$28. three companies that produce titanium concentrates from beach sands are the Travancore Minerals Co., Ltd., Hopkins & Williams (Travancore), Ltd., and F. X. Pereira & Sons (Travancore), Ltd.

Spain.—Plans have been made for the erection of a plant near Gijon, Asturias District, to produce ferrotitanium and other ferro-Workable beach deposits of ilmenite occur in the nearby Districts of Galicia and Coruna and also in the Balearic and Canary

Islands.14

United Kingdom.—Sales of rutile were subjected to official control May 1, 1942, but legitimate consumers were permitted to order as much as 3 months' requirements at a time. 15 Prices of rutile, f. o. b. consumers' works, were fixed at £54 a long ton for Cameroun concentrates, £42-£50 for Indian concentrates, and £45 for Australian concentrates, according to Metal Bulletin. Indian ilmenite, 52-54 percent TiO<sub>2</sub>, was quoted at 28-30 s. per long ton, f. a. s., at the end of 1942.

Wright, Charles Will, Brazil's Strategic Mineral Resources: Min. Cong. Jour., vol. 28, No. 10, October 1942, pp. 38-43.

Foote-Prints, Brazilian Rutile Goes to War: Vol. 15, No. 1, August 1942, pp. 2-8.

Canadian Mining Journal, vol. 63, No. 4, April 1942, p. 272.

Northern Miner, New limenite Show Looks Big: Vol. 28, No. 27, September 24, 1942, p. 9.

Metal Bulletin (London), No. 2709, July 14, 1942, p. 12.

Mining Journal (London), vol. 218, No. 5578, July 18, 1942, p. 29.

Metal Bulletin (London), No. 2710, July 17, 1942, p. 3.

Metal Bulletin (London), No. 2690, May 5, 1942, p. 9.

# MINOR METALS

By Allan F. Matthews 1

## SUMMARY OUTLINE

	Page		Page
Bervllium	819	Indium	825
Boron	821	Lithium	825
Calcium	822	Radium and uranium	826
Cerium	823	Selenium and tellurium	828
Columbium and tantalum	823	Thallium	829
Germanium	825	Zirconium	829

# BERYLLIUM

Beryl requirements for 1943 were estimated at 7,000 short tons by the War Production Board and at 5,000 tons by the Army and Navy Munitions Board. Beryllium in all forms was placed under import control May 4, 1942 (amendment to Order M-63), by the War Production Board and under complete allocation June 1, 1942 (Order M-160). Copper scrap containing 0.1 percent or more Be was directed to be delivered only to companies specifically authorized by the War Production Board, effective March 1, 1943 (Order M-9-b).

Domestic mine production.—Mine shipments of beryl (beryllium concentrates) increased 70 percent in 1942 compared with 1941 and were the largest on record. Beryl is produced in several Western and New England States as a byproduct in mining feldspar, mica, and other pegmatite minerals. Pennington and Custer Counties in the Black Hills of South Dakota furnished 76 percent of the United States

total in 1942 compared with 96 percent in 1941.

Beryl (beryllium concentrates) shipped from mines in the United States, 1938-42

		м	ine shipmen	ts
Year	State		Value	
		Short tons	Total	Average per ton
1938 1939 1940 1941	Maine Colorado, Maine, South Dakota do Maine, New Hampshire, South Dakota, Wyoming Colorado, Maine, New Hampshire, South Dakota	25 95 121 158 269	\$770 2,720 3,721 7,300 24,188	\$30. 80 28. 6z 30. 75 46. 20 89. 92

Prospecting for beryllium ore was very active in 1942. Most promising is a deposit of helvite (sulfosilicate of manganese, iron, and beryllium) at Iron Mountain, Sierra and Socorro Counties, N. Mex., which was examined in some detail by the Bureau of Mines and Geological Survey and found to contain about a million tons of ore averaging 0.4 percent BeO. This quantity is equivalent to some 35,000 tons of beryl, but its availability depends upon development of suitable concentration methods—a problem now being investigated by the Bureau of

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Mines and private interests. During 1942 the Bureau of Mines and the Geological Survey examined beryl deposits in Colorado, Connecticut, Idaho, Maine, New Hampshire, South Dakota, and Virginia. Of 131 pegmatites studied in New Hampshire, 61 were found to contain some beryl.<sup>2</sup> A search for additional sources of beryl in the Black Hills was begun by the South Dakota School of Mines under sponsorship of the General Electric Co., Schenectady, N. Y.

Domestic alloy and compound production.—Beryllium-copper master alloys are made by the Beryllium Corporation of Pennsylvania, Reading, Pa., and by the Brush Beryllium Co., Cleveland, Ohio. Clifton Products, Inc., Painesville, Ohio, a producer of oxide, will enter the alloy field in 1943. The facilities of these three companies are being expanded by commitments of \$1,900,000, \$615,000, and \$200,000, respectively, by the Government-owned Defense Plant Corporation. In addition, the Reconstruction Finance Corporation is loaning \$500,000 to the Beryllium Corporation of Pennsylvania. Metallic beryllium and beryllium compounds are produced by the Brush Beryllium Co. The Calloy Co., Harbor City, Calif., made some test runs on beryllium oxide early in 1942 but had no commercial output during the year. Recent patents on beryllium production have been summarized. \*\*Foreign trade.—Beryl imports declined 27 percent in 1942 compared.

Foreign trade.—Beryl imports declined 27 percent in 1942 compared with 1941, primarily as a result of an Argentine embargo in effect most of the year. Two-thirds of the 1942 imports were entered in January and December. Exports in 1942 comprised 1,531 pounds of beryllium concentrates, 25,256 pounds (\$24,882) of alloys and metal,

and 4,778 pounds (\$9,274) of compounds.

Beryl imported for consumption in the United States, 1938-42, by countries, in short tons

Country of origin	1938	1939	1940	1941	1942
Argentina Brazil India and Dependencies (British India)	78 58	384 75	422 377	861 1, 805	701 915 282
Union of South Africa	10		6		38
Total: Short tons	146 \$5,990 \$41.03	459 \$14, 574 \$31. 75	805 \$23, 865 \$29, 65	2, 666 \$143, 992 \$54. 01	1, 936 (¹) (¹)

<sup>1</sup> Data not available.

Stocks.—Inventories of beryl held by the principal miners, dealers, and consumers in 1942 declined from 2,200 short tons January 1 to 1,400 tons December 31. In addition, the Government-owned Metals Reserve Co. began stock-piling beryl in the third quarter and had

725 tons on hand at the end of the year.

Prices.—Beryl prices continued to climb in 1942, and 10- to 12-percent material brought \$75-\$100 a short ton. Beryllium-copper master alloy (4 percent Be) continued to be quoted at \$15 per pound of contained Be by one producer but was listed at \$17 by the other. Beryllium metal, 96 percent, was quoted at \$47 a pound and beryllium-aluminum at \$40 per pound of contained Be, according to American Metal Market.

<sup>&</sup>lt;sup>2</sup>Olson, J. C., Mica-Bearing Pegmatites of New Hampshire: Geol. Survey Bull. 931-P. 1942, pp. 363-403. 
<sup>4</sup>Light Metals (London), Recent Inventions Relating to Beryllium Alloys: Vol. 5, No. 56, September 1942, pp. 361-363.

Uses.—The principal application of beryllium is in beryllium-copper alloys (0.1-3.5 percent Be; 0-2.6 percent Co, Cr, or Ag; remainder Cu) fabricated into instrument springs, diaphragms, motor parts subject to wear, and low-sparking tools. Beryllium hardens copper and increases its tensile properties without greatly decreasing electrical Beryllium-copper springs have a large amplitude of movement combined with remarkable freedom from elastic driftproperties that enable them to retain stable springiness to a much greater degree than springs made of any other available corrosionresistant material.4 Beryllium oxide is used in white fluorescent lamps and special refractories and the metal 5 as windows in X-ray tubes. Interest in beryllium-aluminum continues, but certain fabricating difficulties remain to be solved. Some raw beryl is ground for use in ceramics.

Foreign production.—Argentine beryl output comes from the Provinces of Córdoba and San Luis, but the reserves of the largest producer (Las Tapias mine in Córdoba) are approaching exhaustion. To assure an adequate ore supply for the beryllium oxide-carbonate plant of Sociedad Anonima Berilo Argentina, Juan Ortiz, Province of Santa Fé, an embargo was placed on beryl early in 1942, but the plant experienced operational difficulties and consumed little ore, so the embargo was lifted October 7. Brazilian beryl comes principally from the States of Paraiba and Rio Grande do Norte. A beryl deposit in the Karibib area of South-West Africa was opened in March 1941 by Jooste Lithium Mines, Ltd. Occurrences of beryl in South Africa and Canada have been described. The Beryllium Smelting Co., Ltd., London, was formed in June 1942 "to carry on business of refiners. and smelters of beryllium and beryllium compounds."

World production of beryl, 1936-42, by countries, in metric tons 1

Country 1	1936	1937	1938	1939	1940	1941	1942
ArgentinaAustralia, Western	300	260	753	299	520	1, 986 (³)	2 784 (8)
Brazil (exports)	4		203	276	1,472	1,703	4 963
Canada (estimate)	. 18 . 89	18 24	15	161	(3)	(3)	(3)
Madagascar (estimated exports)	10	2 21	2 2 265	(3)	(3)	(8)	(3)
PortugalSouth-West Africa	(3)	(3)	(3)	(3)	(3)	20	(8)
Union of South Africa (estimate) United States (mine shipments)	(3)	(8)	(3)	(8)	(3)	(8) 143	(³) 244
Omied Deales (mine surplients)	()	"	20	00	110	140	

<sup>&</sup>lt;sup>1</sup> In addition to countries listed, beryl may also be produced in France, Italy, Norway, Portuguese East Africa, Rumania, and U. S. S. R.

## BORON

Boron was a metallurgical hit of 1942, virtually assuring itself high rank in future among the conventional ferro-alloy elements. The effect of boron on steel is to increase hardenability (depth of hardness); greater ultimate strength and elastic limit are also ob-

<sup>&</sup>lt;sup>2</sup> Exports.

Data not available.
 January to September, inclusive.

<sup>&</sup>lt;sup>4</sup> Carson, Robert W., Springs of Beryllium Copper: Aero Digest, vol. 41, No. 1, July 1942, pp. 150, 153, 272-273.

<sup>5</sup> Claussen, G. E., and Skehan, J. W., Malleable Beryllium: Metals and Alloys, vol. 15, No. 4, April 1942, pp. 599-603.

<sup>6</sup> Chubb, W. F., Beryllium—Its Economics and Technology: Light Metals (London), vol. 5, No. 52, May 1942, pp 156-164.

tained. Boron additions of 0.003 percent can substitute for 1 percent nickel, 0.3 percent chromium, 0.2 percent manganese, 0.12 percent vanadium, or 0.1 percent molybdenum.8 Thus, the incorporation of boron in NE (National Emergency) steels enables the quantities of strategic metals used to be reduced without impairing quality. a new discovery, boron in steel has been adopted as a result of fuller realization that only quantities as small as 0.001 to 0.003 percent give optimum results and that much excess causes hot shortness and produces brittle steel. Boron is introduced as ferroboron (10-20 percent B), boron-silicon (Borosil), or one of a series of complex alloys (0.2-2 percent B) such as Grainal, Bortam, Carbortam, Silvaz, or Silcaz.

In cast iron 0.02-0.12 percent boron reportedly increases hardness, refines the grain, and improves wearing qualities, although it also reduces malleability. Boron is a strong deoxidizer, and its use to remove oxygen and nitrogen from copper alloys is said to increase the mechanical soundness and electrical conductivity of castings.

Salts of boron are discussed in the Magnesium Compounds and Miscellaneous Salines chapter of this volume.

## CALCIUM

Production of calcium metal was increased in 1942 by the principal producer—the Electro Metallurgical Co., Sault Ste. Marie, Mich. The metal was informally placed under Government allocation control at the beginning of 1943, and a conventional War Production Board order was expected by the middle of the year. Calcium-silicon was subjected to direct allocation by the Office of Production Management July 29, 1941 (Order M-20), which was revised November 29, 1941 (Order M-20-a), and extended indefinitely May 30, 1942 (Amendment 1). Calcium-silicon was imported from Canada in 1942 and from France in 1941. Calcium metal, 97-98 percent, ton lots, continued to be quoted at \$1.25 a pound in 1942. According to Metals & Metallurgical Industries, calcium-silicon, ton lots, was 16½ cents a pound, f. o. b. Welland, Ontario. Metallic calcium, calcium-silicon, and other calcium alloys are used primarily in deoxidizing steel.9 Additions of up to 0.25 percent calcium in some magnesium castings reduce the heat-treating time and result in an improved surface.

Calcium metal and calcium-silicon imported for consumption in the United States, 1938-42

Commodity	1938	3	193	9 19		1940		1941		2
Commodity	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value
Calcium metal Calcium-silicon	41, 299 1, 402, 314	\$16, 144 77, 003	41, 718 3, 972, 571	\$17, 758 <b>22</b> 5, 312	11, 900 2, 131, 758	\$6, 518 154, 424	111, 994	\$8, 337	60, 300	\$10, 144

<sup>&</sup>lt;sup>7</sup> Comstock, George F., Effects of Eight Complex Deoxidizers on Some 0.40-Percent Carbon Forging Steels: Trans. Am. Inst. Min. and Met. Eng., vol. 150, 1942, pp. 408–420. Metals Technol., vol. 9, No. 1, January 1942, Tech. Pub. 1417, 13 pp. Lippert, T. W., Boron: Iron Age, vol. 150, No. 21, November 19, 1942, pp. 41–44. Tisdale, Norman F., Boron—A New Vitamin for Steel and Cast Iron: Metal Progress, vol. 41, No. 3, March 1942, pp. 330–331.

STisdale, Norman F., Boron Steels Increasingly Favored: Iron Age, vol. 151, No. 5, February 4, 1943, pp. 40–44.

PEinerl, Otto, and Neurath, Frederic, The Alkaline Earth Metals and Their Alloys—Increasing Technical Importance: Chem. Age (London), vol. 47, No. 1205, August 1, 1942, pp. 107–111. pp. 107-111. Sanderson, L., Calcium: Canadian Min. Jour., vol. 63, No. 12, December 1942, pp.

## CERIUM

Ferrocerium, the principal pyrophoric (sparking) alloy, was in strong demand during 1941 and 1942 as a constituent of cigarette lighters for our armed forces and particularly for export to the United Kingdom under Lend-Lease agreement. The supply was provided by the Cerium Metals Corporation (formerly American Treibach Chemical Works), Niagara Falls, N. Y., and by Shawinigan Chemicals, Ltd., Shawinigan Falls, Quebec, Canada. Imports of cerium alloys from Canada, only foreign source since the outbreak of war, totaled 11,573 pounds (\$65,549) in 1942 compared with 20,-190 pounds (\$90,948) in 1941 and 462 pounds (\$1,611) in 1940. Exports of cerium alloys and metal were 26,016 pounds (\$84,739) in 1942. Cerium metal was quoted by Metal Bulletin (London) at £7 5s. a pound and the 52-percent alloy at 35s. a pound at the close Ferrocerium is used in cigarette lighters and acetylenewelding torches and as a metallurgical refining agent. Cerium metal finds application in the evacuation of radio tubes. The principal ore of cerium is monazite, described in the Minor Nonmetals chapter of this volume.

### COLUMBIUM AND TANTALUM

Columbium (niobium) and tantalum ores were placed under import control by the War Production Board April 9, 1942 (Amendment 4, Order M-63). Full allocation control of tantalum in all forms was instituted May 22, 1942 (Order M-156), and of ferrocolumbium March 25, 1943 (Order M-296). Columbium and tantalum ores (columbite and tantalite) are invariably mixtures, designated one or the other depending on the relative content of Cb<sub>2</sub>O<sub>5</sub> and Ta<sub>2</sub>O<sub>5</sub>. The Government stock pile held by the Metals Reserve Co. included no columbite but 427,756 pounds of tantalite at the end of 1942 and 1,016 pounds of columbite and 321,867 pounds of tantalite March 8, 1943.

Domestic production.—Some 1,000 pounds of tantalite-columbite was produced in South Dakota and Wyoming in 1941-42, but only 200 to 250 pounds was shipped each year. The sole domestic producer of ferrocolumbium is the Electro Metallurgical Co., Niagara Falls, N. Y., and the principal producer of tantalum metal and compounds is the Fansteel Metallurgical Corporation, North Chicago, Adjunctive to its original plant, the latter company in the name of its subsidiary—the Tantalum Defense Corporation—is erecting facilities for which the Government-owned Defense Plant Corpora-

tion has provided \$4,225,000.

Tantalite shipped from mines and columbite and tantalite imported for consumption in the United States, 1938-12

				·				
		pments of	Imports					
Year	tanta	alite 1	Colu	mbite	Tantalite .			
	Pounds	Value	Pounds	Value	Pounds	Value		
1938 1939 1940	36, 189 340	\$35,127 200	645, 141 109, 132 595, 220	\$228, 078 37, 062 210, 526	41,706 56,561	\$80, 092 82, 990		
1941 1942	250 200	<sup>2</sup> 219 <sup>3</sup> 175	1, 440, 455 1, 762, 355	504, 537 608, 917	490, 460 403, 464 575, 799	258, 514 188, 936 481, 230		

<sup>1</sup> Includes some columbite.

<sup>2</sup> Revised estimate.

Foreign trade.—Columbite imports comprised 1,724,800 pounds from Nigeria, 36,422 from Belgian Congo, and 1,133 from Brazil in 1942; and 1,435,312 pounds from Nigeria, 2,914 from Argentina, and 2,229 from Brazil in 1941. Tantalite imports included 309,843 pounds from Belgian Congo, 224,835 from Brazil, 18,971 from Southern Rhodesia, 17,380 from India, and 3,300 from Canada in 1942; they totaled 161,996 pounds from Brazil, 146,904 from Belgian Congo, 64,773 from South-West Africa, 29,574 from Australia, and 217 from the Union of South Africa in 1941. Exports in 1942 comprised 200 pounds (\$277) of ferrocolumbium, 266 pounds (\$18,475) of tantalum metal and alloys, and 179 pounds (\$2,595) of tantalum compounds.

Prices.—Columbite (about 65 percent) was selling at 50-56 cents per pound of contained Cb<sub>2</sub>O<sub>5</sub> early in 1943. The Metals Reserve Co. purchased tantalite during 1942 at \$1.25 per pound of contained  $Ta_2O_5$  for 40-percent material, \$1.75 for 50-percent, \$2.15 for 60-percent, and \$2.60 for 70-percent material. Ferrocolumbium, 50-55 percent, was quoted by Metal and Mineral Markets at \$2.25-\$2.30 per pound of contained Cb, f. o. b. Niagara Falls. Columbium metal continued to be listed at \$227-\$254 a pound and tantalum metal at

\$65-\$73 a pound.

Uses.—The addition of 0.5 to 0.8 percent columbium to stainless steels 10 has been found to improve weldability, creep strength, and impact strength. One application is aircraft exhaust stacks, manifolds, and collector rings. Tantalum is used principally in electronic tubes and carbide tools and as a catalyst in producing butadiene synthetic rubber. Smaller quantities go into corrosion-resistant equipment for chemical plants and into aerial camera lenses. The glass for these lenses is a mixture of tantalum, tungsten, lanthanum, and boron oxides without silica and combines high refractivity and low dispersion, resulting in a lense that can be used at high altitudes with no loss of definition or coverage. Tantalum metal is recommended for

skull plates.11 Foreign production.—Nigeria produced 623 metric tons of columbite and exported 862 tons in the first 9 months of 1942, according to the War Production Board. The Jantar Nigeria Co., Ltd., principal producer, mined 424 metric tons of columbite and shipped 711 tons during the year ended September 30, 1942; proved ore reserves at that time were 4,800 tons, and the expected output for the 1943 fiscal year was 500 tons, all under contract to American buyers.<sup>12</sup> A pilot plant for producing columbium oxide has been built in England.13 Belgian Congo was producing about 11 metric tons of tantalite monthly in mid-1942, according to the War Production Board. Brazilian exports of tantalite-columbite were stated by the Board of Economic Warfare to be 94 tons in 1941. Moneta Mines, Ltd., opened a tantalite deposit in 1942 between Malartic and Amos, Quebec, Canada.14

Jo Clark, C. L., Influence of Columbium or Titanium Additions to 5 Cr-Mo Steel: Oil and Gas Jour., vol. 40, No. 27, April 2, 1942, pp. 39-41; No. 50, April 23, 1942, p. 72. Riegel, Emil Raymond, Industrial Chemistry: Reinhold Publishing Corporation, New York, 4th ed., 1942, pp. 799, 818-819.

"Pudenz, Lieut. (j.g.) Robert H., The Repair of Cranial Defects with Tantalum: Jour. Am. Med. Assoc., vol. 121, No. 7, February 13, 1943, pp. 478-481.

Med. Assoc., vol. 121, No. 7, February 13, 1943, pp. 478-481.

Med. Assoc., vol. 121, No. 7, February 13, 1943, pp. 12.

Horne, W. P., A Note on the Experimental Production of Mixed Oxides of Tantalum and Niobium from Nigerian Columbite: Bull. Inst. Min. and Met. (London), No. 458, January 11, 1943, 5 pp.

ary 11, 1943, 5 pp.

14 Canadian Min. Jour., vol. 63, No. 9, September 1942, p. 614.

## GERMANIUM

Germanium in small quantities (often about 0.01 percent) occurs in zinc and copper ores, but it has never been recovered on a commercial scale in the United States. A pilot plant erected by the Eagle-Picher Mining & Smelting Co., Henryetta, Okla., to treat cadmium byproducts yielded small quantities of germanium metal, oxide, and chloride during 1942. Uses for germanium are reported occasionally, but none have appeared sufficiently promising to induce the War Production Board to stimulate domestic production or importation from South-West Africa of a quantity of germanium residue obtained as a byproduct of smelting Tsumeb copper-lead-zinc ores. Germanium metal was quoted by suppliers of rare metals at \$3-\$5 a gram in New York and 19s. 6d. a gram in London at the close of 1942, but commercial grades were available at lower prices.

## INDIUM

Domestic production.—Indium metal production in the United States in 1942 increased several-fold over 1941. Virtually the entire 1942 output-byproduct of zinc and lead operations-was produced by the Anaconda Copper Mining Co., although the Eagle-Picher Mining & Smelting Co. had a small pilot-plant yield. Some indium has been produced in past years by the American Metal Co., Ltd., American Smelting & Refining Co., and National Zinc Co., Inc., and these companies marketed some metal from stock during 1942. The Indium Corporation of America, principal distributor, owns a property near Kingman, Mohave County, Ariz., where there is reputedly blocked out 50,000 tons of zinc ore averaging about 2 troy ounces of indium per The increasing demand for indium is expected to result in early exploitation of this deposit.15

Prices.—The price of indium metal, commercial grade (98 percent), according to Metal and Mineral Markets was \$12.50 a troy ounce during most of 1942 but was reduced to \$10 an ounce (\$146 an avoirdupois pound), effective December 23. Electrolytic-grade indium (99.9 percent) was reduced on the same date from \$30 to \$15 an ounce.

Uses .- Cadmium-nickel and copper-lead bearings for aircraft, truck, and marine engines are coated with indium to resist the corrosive action of acids in lubricants, and this application absorbed most of the indium consumed in 1942. The life of bronze bearings in a certain heavy-duty screw machine was lengthened greatly by indium treatment. Additions of 1 to 2 percent indium to lead-silver solders improve coverage, spreadability, and bonding strength. In general, indium coatings 0.0005 to 0.001 inch thick on nonferrous metals improve resistance to corrosion and abrasion and present a lustrous finish.

Foreign production.—The Consolidated Mining & Smelting Co. of Canada, Ltd., Trail, British Columbia, began to produce indium in 1941. Indium has also been produced commercially in Germany,

Belgium, and possibly Japan and U.S.S.R.

## LITHIUM

Production facilities for lithium metal were greatly expanded during 1942. Nevertheless, supply could not pace demand, so the War

Ludwick, M. T., Indium: Steel, vol. 111, No. 19, November 9, 1942, pp. 80-81, 122-124.
 Metal Finishing, Indium Solders: Vol. 40, No. 11, November 1942, pp. 594, 596.

Production Board instituted allocation control of the metal and compounds September 1 (Order M-191) and of the ores December 5 (Order M-253). Lithium ores are discussed in the Minor Nonmetals chapter of this volume. Lithium has a strong affinity for gases and impurities in molten metal, and its addition to copper-base alloy melts in the form of lithium-copper (2 percent Li), lithium-zinc (2 percent Li), or lithium-calcium (50 percent Li) results in sounder castings and higher conductivity. The use of lithium as a scavenger in cast iron and steel is also developing. Lithium in small quantities (0.04-0.1 percent) is reported to improve the physical properties of various lead, zinc, aluminum, and magnesium alloys. Addition of 0.12 percent lithium to a silver brazing solder increased fluidity, strength, and melting properties.17 Lithium metal, 98-99 percent, 100-pound lots, was quoted at \$15 a pound throughout 1942, according to Metal and Mineral Markets.

## RADIUM AND URANIUM

Industrial radiography absorbed over half of the new supply of radium in 1942, and most of the rest went into luminescent paints. There were virtually no Government controls on the delivery, price, or use of radium and uranium in the United States in 1942; but effective January 26, 1943, the War Production Board prohibited the use of uranium in ceramics (Order M-285). Research on uranium progressed appreciably in 1941-42, and in the interest of secrecy the War Production Board relinquished to the War Department the

supervision of supply and distribution.

Domestic production.—Carnotite is mined in Arizona, Colorado, and Utah for recovery of vanadium, radium, and uranium.18 Grinding tests on these ores were conducted recently by the Bureau of Mines.19 Increased production of vanadium has yielded large quantities of uranium in concentrates and tailings, but it is not known to what extent these have been processed. The domestic output of radium in 1942 was 2.6 grams, all refined by the Vitro Manufacturing Co., Pittsburgh, Pa. The S. W. Shattuck Chemical Co., Denver, Colo., devoted its facilities principally to molybdenum compounds and thus produced no radium. The two companies had material in stock at the end of 1942 containing about 1 gram of radium each. These companies and the Vanadium Corporation of America (Naturita, Colo.) are producers of uranium compounds.

Foreign trade.—All the radium, radioactive substitutes, and uranium imported in 1941-42 came from Canada, except entries of 100 milligrams of radium from Belgium (originally) and 525,559 pounds of uranium ore from Belgian Congo in 1942 and 53,090 pounds of uranium compounds from Belgian Congo in 1941. Exports in 1942 comprised 1,245 grams (\$58,997) of radium-bearing compounds, 2 milligrams (\$8) of mesotherium compounds, 543 grams (\$1,076) of uranium concentrates, and 426 pounds (\$1,827) of uranium com-

pounds.

<sup>17</sup> Hensel, F. R., Larsen, E. I., and Swazy, E. F., A Lithium-Bearing Silver Solder: Metals and Alloys, vol. 15, No. 6, June 1942, pp. 962–965,

18 Fischer, Richard P., Vanadium Deposits of Colorado and Utah—A Preliminary Report: Geol. Survey Bull. 936–P, 1942, pp. 363–394.

Kelly, Sherwin F., Geological Studies of Vanadium-Uranium Deposits by Geophysical Exploration Methods: Min. Cong. Jour., vol. 27, No. 8, August 1941, pp. 27–35.

19 Shelton, S. M., and Engel, A. L., Progress Reports—Metallurgical Division. 55, Dry Differential Grinding Tests of Carnotite Ores: Bureau of Mines Rept. of Investigations 3636, 1942, 32 pp.

Radium salts, radioactive substitutes, and uranium ore and compounds imported for consumption in the United States, 1938-42

	I	Radium sal	ts	Radio-	Troni	ım ore	Uranium oxide and salts		
Year		Va	lue	active substi-	Oram				
	Grams	Total Averager g		tutes (value)	Pounds	Value	Pounds	Value	
1938	38. 75 78. 631 30. 311 4. 412 23. 043	\$787, 025 1, 953, 820 748, 097 110, 202 377, 326	\$20,300 24,800 24,700 25,000 16,400	\$5,746 966 5,650 13 50	2, 400, 198 541, 307	\$10 2, 110, 927 806, 919	376, 708 1, 439, 324 240, 199 387, 505 377, 398	\$520, 540 1, 197, 786 388, 355 501, 370 851, 098	

Prices.—Radium was nominally quoted at \$25 a milligram during 1942. Some sales at \$25-\$27.50 were reported, but probably most were nearer \$20 a milligram. Orange or yellow uranium oxide and sodium uranate were listed by Glass Industry unchanged at \$1.65 a pound during 1942; black uranium oxide was quoted at \$2.55 a

pound until December, when the price was reduced to \$2.15.

Uses of radium.—Most of the radium in current use is for the treatment of cancer and skin diseases. However, over half of the new supply is employed in radiographic inspection of castings, forgings, and welds. In many instances of both medical and industrial radiography, radium emanations and X-rays can be utilized interchangeably. Radium coatings on watches, gun sights, compasses, and other instrument dials permit observation in the dark. Radium and beryllium mixtures project neutrons for petroleum exploration 20 and scientific research. The number of radioactive specimens tested annually by the National Bureau of Standards gives some index as to demand. Such specimens contained 16,408 milligrams of radium and 2,139 milligrams of mesothorium in 1942 compared with 19,928 and 1,451 milligrams, respectively, in 1941. Mesothorium is a radium substitute obtained from monazite residues. The National Bureau of Standards recently outlined safe practices in handling radioactive compounds in the dial-painting industry (Handbook 27) and gave suggestions for the protection of radium during air raids (Handbook 38). Polonium, a byproduct of radium, is a radioactive element used in spark plugs.21

Uses of uranium.—The principal peacetime outlet for uranium is as a colorant in ceramics, but this use was prohibited in January 1943 to assure ample supplies for research on uranium isotope 235 as a source of energy 22 and for consumption in special steels, luminescent

paints, photographic reagents, and other chemicals.

Foreign production.—Eldorado Gold Mines, Ltd., reopened its pitchblende mine at Great Bear Lake, Northwest Territories, Canada,28 in 1942 after a 2-year shut-down. Its refinery at Port Hope, Ontario, continued to operate during the interim on accumulated concentrates and in 1942 reportedly ran close to its capacity of 8 or 9

<sup>&</sup>lt;sup>20</sup> Pontecorvo, Bruno, Neutron Well Logging—A New Geological Method Based on Nuclear Physics: Oil and Gas Jour., vol. 40, No. 18, September 11, 1941, pp. 32-33.

<sup>21</sup> Dillon, J. H., and Street, J. W., Large-Scale Extraction of Polonium from Active Lead and Formation of Radioactive Electrode Alloys: Jour. Appl. Physics, vol. 13, No. 3, March 1942, pp. 189-198.

<sup>22</sup> De Ment, Jack, and Dake, H. C., Uranium and Atomic Power: Chemical Publishing Co., Inc., Brooklyn, 1941, 335 pp.

<sup>23</sup> Camsell, Charles, Discovery and Development of Radium at Great Bear Lake: Jour. Franklin Inst., vol. 233, No. 6, June 1942, pp. 545-557.

grams of radium and 40 short tons of uranium compounds monthly. The radium-uranium mine in Belgian Congo, owned by Union Minière du Haut Katanga, remained inoperative in 1942, although a few hundred tons of ore were shipped from stock to the United British-owned Urgeirica Radium, Consolidated, produced all of Portugal's output in 1941—330 metric tons of uranium ore (1-1.8 percent U<sub>3</sub>O<sub>8</sub>) and 772 kilograms of radioactive barium sulfate containing 5.8 grams of radium.

## SELENIUM AND TELLURIUM

Domestic production.—Selenium and tellurium production declined 18 and 0.2 percent, respectively, in 1942 compared with 1941, and producers' shipments slumped more than 50 percent. Thus, in 1942 producers maintained their output relatively close to the 1941 peak even in face of a drastic decline in demand, hoping, apparently, that current uses would expand or that the shortage of common metals would promote development of new uses for selenium and tellurium and thereby provide an outlet for their mounting stocks. Some tellurium is a byproduct of lead, but all the selenium and most of the tellurium recovered come from the tank slimes of electrolytic copper refineries. Annual plant capacity for selenium and tellurium production is approximately 750,000 and 300,000 pounds, respectively, but actual capacity for the former is limited by the availability of selenium slimes.

Salient statistics of elemental selenium and tellurium in the United States. 1938-42

		•	Selenium	•		1	Tellurium	
Year	Production	Producers'	Producers' stocks at	Imp	orts 3	Production	Producers'	Producers'
	(pounds)	(pounds)	end of year (pounds)	Pounds	Value	(pounds)	sales <sup>2</sup> (pounds)	end of year (pounds)
1938 1939 1940 1941 1942	225, 674 227, 131 328, 731 620, 493 506, 426	166, 494 345, 726 368, 709 681, 650 316, 613	365, 400 246, 800 206, 800 146, 000 341, 900	101, 034 124, 830 134, 429 197, 873 83, 666	\$163, 598 193, 168 198, 163 288, 161 127, 004	11, 076 25, 234 85, 622 224, 639 224, 132	26, 944 63, 431 88, 996 239, 983 98, 798	77, 300 39, 100 35, 700 20, 400 145, 700

Includes tellurium content of small quantity of oxide.
 Bureau of Mines not at liberty to publish value. Quantities for 1942 represent producers' shipments.

3 Includes s elenium salts

Foreign trade.—Except for an unspecified quantity valued at \$5 from the United Kingdom in 1942, all selenium imports in 1941-42 came from Canada. Tellurium is not shown in import statistics, except in combination with other commodities. Producers reported exporting 5,550 pounds of selenium (including Se content of compounds) and 150 pounds of tellurium in 1942 compared with 23,169 pounds of selenium and no tellurium in 1941. Dealers doubtless exported additional quantities.

Prices.—The base price of selenium (black powdered, 99.5 percent) and of tellurium continued to be \$1.75 a pound throughout 1942. Glass Industry quoted barium selenite and sodium selenite at \$1.40-

\$1.65 a pound.

Uses.—The largest consumer of selenium is the glass industry, which uses it as a red colorant and (in smaller additions) as a

の はははいいて からになる あるから あっこん

LANCE TO SERVICE THE PARTY OF T

decolorizer. Most of the tellurium supply and some selenium are added to rubber cable coverings to promote resistance to heat, oxidation, and abrasion and to increase resilience. Additions of selenium and tellurium improve the machinability of stainless steels and copper alloys.<sup>24</sup> Formerly made of silver-plated brass, cable connectors of tellurium-copper (combining high machinability and electrical conductivity) are going into aircraft, torpedo boats, tanks, and trucks.<sup>25</sup> Coatings of red selenium on magnesium alloys to resist attack by sea water have found considerable application in Europe. Cadmium sulfoselenide pigments (red, maroon, and orange) were in wide use until the cadmium shortage. Tellurium toughens lead and is now substituting for chromium in the development of wear-resistant surfaces on gears, wheels, and other cast-iron products. Uses of selenium and tellurium are described in a comprehensive paper by several research men at Battelle Memorial Institute.<sup>26</sup>

#### THALLIUM

Thallium output was stepped up in 1942 by the sole domestic producer, the American Smelting & Refining Co., which recovers the metal as a byproduct of zinc-cadmium operations at its Globe refinery, Denver, Colo. Thallium has been produced in Belgium, France, Germany, and Poland, and cessation of imports from these countries has resulted in a shortage of thallium in the United States. Thallium metal is quoted at \$10 a pound by Metal and Mineral Markets and sulfate at \$5-\$7 a pound by Oil, Paint and Drug Reporter. Most of the thallium supply is consumed in the form of sulfate, an odorless, tasteless poison used in rodent and ant control. Consumption of thallium sulfate was 3,500 pounds in 1942, according to an estimate by the Department of Agriculture. Thallium oxysulfide is sensitive to wave lengths in the infrared and is therefore useful in "dark signaling." Thallium-lead alloys containing 3-65 percent Tl are among the most insoluble alloys known.

#### ZIRCONIUM

No use or price control was imposed on zirconium in 1942, but the War Production Board placed the concentrates under import control December 27, 1941 (Order M-63). The Government-owned Metals Reserve Co. began stock-piling zirconium concentrates in 1942 and by the end of the year had on hand 4,590 short tons of zircon and 4,156 tons of baddeleyite. The Government purchased zircon only as an inducement to processors to increase the supply of rutile obtained from Australian mixed zircon-rutile concentrates.

Domestic production.—Zircon production in the United States amounted to a few hundred tons in 1942 compared with somewhat smaller quantities in 1941 and 1940, no output in 1929-39, and 3,646 short tons in 1927. The only domestic producer at present is the Riz Mineral Co., which recovers zircon as an accessory of rutile and ilmenite from beach sands near Melbourne, Fla. At the beginning of

<sup>&</sup>lt;sup>24</sup> Bailey, G. L., and Hallowes, A. P. C., The Properties of Commercial Coppers Containing Selenium, Tellurium, and Bismuth: Metal Ind., vol. 62, No. 1, January 1, 1943, pp. 6-9; No. 2, January 8, 1943, pp. 18-20.

Butzner, J. I., Nonferrous Metals: Iron Age, vol. 151, No. 1, January 7, 1943, pp.

<sup>141-142.
&</sup>lt;sup>20</sup> Waitkins, G. R., Bearse, A. E., and Shutt, R., Industrial Utilization of Selenium and Tellurium: Ind. and Eng. Chem., ind. ed., vol. 34, No. 8, August 1942, pp. 899-910.

1942 E. S. Curtis set up a pilot plant on the Fay Placers Mining Co. property, Lincoln, Calif., to determine the feasibility of producing zircon as a byproduct of gold dredging, but the results indicated that such production was not economical at current price levels and the plant was dismantled in May. Tests on concentration of zircon from

Oregon beach sands were conducted by the Bureau of Mines.<sup>27</sup>

Foreign trade.—Imports of zirconium concentrates included 18,259 short tons from Australia, 15,283 from Brazil, and 196 from India in 1942 compared with a total of 21,709 from Australia, 5,002 from Brazil, and 963 from India in 1941. The Australian concentrates are nearly half zircon and also contain appreciable quantities of rutile and ilmenite. (See Titanium chapter of this volume for details.) The Brazilian zirconium concentrates are essentially baddeleyite containing 70 to 85 percent ZrO<sub>2</sub>. Exports in 1942 comprised 30 tons (\$2,104) of zirconium concentrates, 166 tons (\$169,729) of zirconium alloys and metal, and 201 tons (\$65,975) of zirconium compounds.

Zirconium concentrates and zirconium ferro-alloys imported for consumption in the United States, 1938-42

	Zirconium co	ncentrates 1	Zirconium ferro-alloys			
Year	Short tons	Value	Pounds	Value		
1938	2, 093 3, 433 16, 845	\$62, 138 49, 919 252, 749	244, 126 799, 269 533, 055	\$13, 520 50, 169 37, 126		
1941 1942	27, 674 33, 962	604, 744 817, 702				

<sup>&</sup>lt;sup>1</sup> Classified as "Ore" by Department of Commerce. Includes zircon-rutile-ilmenite concentrates from Australia.

Prices.—Metal and Mineral Markets continued to quote zirconium ore, 55 percent ZrO<sub>2</sub>, at \$60-\$70 a short ton, f. o. b. Atlantic seaboard; zirconium ferrosilicon at \$102.50-\$107.50 a long ton for 12- to 15-percent Zr content and 14-16 cents a pound for 35-40 percent Zr; and

powdered zirconium metal at \$7 a pound.

Uses.—Most of the zirconium supply goes into ceramics, chiefly as an opacifier in porcelain enamels and pottery glazes but also as a constituent of refractories, electrical and chemical porcelains, grinding balls, and glasses resistant to heat and chemicals. Metallurgically zirconium is a deoxidizer and scavenger; and small additions to certain steels are said to improve hot-working properties, surface characteristics, and impact strength. Zirconium-copper is a promising alloy that combines high heat conductivity and tensile strength. Ductile zirconium metal is used in electronic tubes, lamp filaments, and welding rods, and the metal powder in flares, photoflash bulbs, and blasting caps. In addition to ceramics, zirconium compounds go into white leather, resins, dye extenders, water repellents, and catalysts.

<sup>&</sup>lt;sup>27</sup> Dasher, John, Fraas, Foster, and Gabriel, Alton, Mineral Dressing of Oregon Beach Sands. 1. Concentration of Chromite, Zircon, Garnet, and Ilmenite: Bureau of Mines Rept. of Investigations 3668, 1942, 19 pp. 28 Metal Industry (London), Copper-Zirconium: Vol. 61, No. 4, July 24, 1942, p. 49.

## PART III. NONMETALS

## RITUMINOUS COAL AND LIGNITE 1

## SUMMARY OUTLINE

			Page
	Page		_
Survey of the bituminous-coal and lignite in-	4	Final bituminous-coal and lignite statistics for	
dustry in 1942	831	1941—Continued.	100
Sources of data	834	Bituminous coal and lignite loaded for ship-	
Sources of data	835	ment by individual railroads and water-	
Salient statistics		TRATE	864
Production by weeks and months	835	Methods of recovery	869
Consumption	838	Stripping operations	871
Fuel efficiency	838	Stripping operations	876
Relative rate of growth of coal, oil, and water		Power drilling	
power	839	Mechanical loading in underground bitumi-	088
Distribution	844	nous-coal and lignite mines	877
Stocks held by consumers	846	Mechanical cleaning	883
Final bituminous-coal and lignite statistics	• • • •	Detailed statistics, by States and counties	887
	847	Statistics on lignite in 1941	904
for 1941	848	Production	904
Salient trends		Number and size of mines	906
Summary by States		Methods of recovery	906
Production by weeks and months	855	Ottiin-anapations	
Number and size of mines	858	Stripping operations	
A verage value	860	Imports and exports	
Labor statistics	861	World production	910

## SURVEY OF THE BITUMINOUS-COAL AND LIGNITE INDUSTRY IN 1942

In response to the increased need for coal to keep the war economy moving, the production of soft coal was pushed to an all-time high in 1942 estimated at 580,000,000 net tons, which surpassed the previous peak of 579,385,820 net tons mined in 1918. Owing to the Government program to encourage summer storage of coal, there was less seasonal decline than for any year on record. The regularity of production in 1942 was in striking contrast with 1941. During the first quarter of 1941 production was high to fill orders purchased for storage by consumers in anticipation of possible suspension of mining when the wage contract expired on March 31. Output was largely at a standstill in April pending the signing of a new wage contract.

Production.—The 1942 output—580,000,000 net tons—was a 13-percent increase over 1941. An outstanding feature related to this production was the elimination of seasonal declines, due largely to the Government program urging consumers to build up stocks during the Throughout most of the year production remained well

above 11,000,000 net tons per week.

Consumption.—Each of the major classes of consumers except steel and rolling mills used more coal in 1942 than in 1941; the increase

The collection of statistics on the bituminous-coal industry which before 1937 was conducted by the Bureau of Mines is now performed by the Bituminous Coal Division, U. S. Department of the Interior, Dan H. Wheeler, Director.

Material in this chapter was prepared in the Division's Economics Branch under the supervision of G. A. Lamb, chief. It was completed under the immediate direction of W. H. Young, in collaboration with R. L. Anderson, M. E. McMillan, and R. M. McKinney.

<sup>1</sup> Data for 1942 are preliminary; detailed statistics with final revisions will be released later. Data for

ranged from 23 percent for beehive coke ovens to 4 percent for coal-gas retorts. Consumption by steel and rolling mills, for uses other than making coke, declined 4 percent in 1942 compared with 1941.

Changes in stocks.—The reserve supply of coal in the hands of industrial consumers and retail coal yards rose from a total of 62,-737,000 net tons at the beginning of 1942 to 85,889,000 net tons at the close. The days' supply of stocks advanced from 40 to 51. Between the same periods stocks on the upper Lake docks declined 1,418,621 net tons, while unbilled coal in cars at the mines or classification yards fell 780,000 net tons.

Distribution.—Shipments of bituminous coal and lignite during 1942 rose substantially above the 1941 level in each of the primary channels of distribution except in Lake Erie loadings, which decreased slightly. Table 9 shows trends in distribution of bituminous coal for




FIGURE 1.—Trends of production, stocks, and prices of bituminous coal and lignite in the United States, 1933-42.

1937-42. Changes in the monthly volume of the more important

movements are shown in figure 7.

Mechanization.—Coal loaded mechanically at underground mines in the United States continued to advance sharply during 1941. The quantity of soft coal mechanically loaded expanded from 147,870,252 net tons in 1940 to 186,667,250 in 1941, an increase of 26 percent. The percentage of total underground bituminous and lignite production mechanically loaded increased from 35 in 1940 to 41 in 1941.

Mechanical cleaning.—Bituminous coal mechanically cleaned by wet and pneumatic methods in the United States (exclusive of Alaska) rose from 102,205,186 net tons in 1940 to 117,469,857 in 1941, an increase of 15 percent. There are no mechanical cleaning plants at

lignite mines.

Trend of employment.—An estimate of the average number of men employed at bituminous-coal and lignite mines in 1942 indicates a slight rise to 460,000 men from 456,981 in 1941. The estimate is based largely on monthly indexes of employment compiled by the Bureau of Labor Statistics.

Index to capacity.—The potential output upon a 308-day basis was 733,000,000 net tons in 1941. Under the 5-day week, full-time operation is limited to approximately 261 days. The average output per working day was 2,380,321 tons during 1941, which (if applied to 261




FIGURE 2.—Average production of bituminous coal and lignite in the United States per working day in each month, 1915-42.

days) gives an annual potential output of 621,000,000 tons compared

with the actual total production of 514,149,245 tons.

Trend of fuel efficiency.—For many years before 1942 there was a steady trend toward increased fuel efficiency. During 1942 this trend was arrested or reversed, and some industries exhibited decreased fuel efficiency (see table 5).

Competition of oil and gas.—Competition of coal with oil and gas in 1942 was overshadowed by the necessity of making the best possible use of the fuels available and satisfying the unprecedented fuel requirements of a war economy. Rationing of fuel oil in the Eastern States was accompanied by extensive conversion from oil to coal, particularly with respect to industrial fuel-burning facilities.

Electric power utilities consumed 6 percent more bituminous coal and 14 percent more gas in 1942 than in 1941, while decreasing their

use of fuel oil by 24 percent.

The consumption of coal in 1942 by class I line-haul railroads increased 19 percent over 1941, and fuel-oil consumption by class I line-haul, switching, and terminal railroads increased 23 percent.

In domestic heating the effect of curtailment of the manufacture and sale of certain types of fuel-burning equipment is shown by Bureau of the Census data. Sales of domestic stokers dropped from 158,734 in 1941 to 62,753 in 1942, a decrease of 60 percent; and shipments of domestic oil-burners, boiler-burner units, and furnace-burner units fell from 271,673 to 82,357, a decrease of 70 percent.

## SOURCES OF DATA

Bituminous-coal and lignite production statistics for 1942 are preliminary estimates based upon (1) weekly or monthly reports of railroad carloadings of coal and beehive coke by all the important carriers, (2) shipments by river as reported by the United States Army Engineers, (3) direct reports from a number of mining companies, and (4) monthly production statements compiled by a number of local operators' associations and State mine departments. In the estimates for 1942, allowance has been made for commercial truck shipments, local sales and colliery fuel, and small trucking or wagon mines producing

over 1,000 tons a year.

The 1941 bituminous-coal statistics were compiled by the Bituminous Coal Division, and 1941 statistics on lignite and certain semi-anthracite mines in Montgomery and Pulaski Counties, Va., were compiled by the Bureau of Mines. Data for 1941 are final and are based upon detailed annual reports of production and mine operation furnished by the producers. As in previous years, all but a small percentage of the output was covered by the reports submitted. For the remaining output not directly reported, consisting chiefly of small mines, it has been possible to obtain reasonably accurate data from the records of the State mine departments, which have statutory authority to require such reports or, in a few instances, from railroad carloadings.

Final production of bituminous coal and lignite for 1941 was 514,-149,245 net tons. This differ slightly from 515,769,248 net tons, as published in May 1943 in Mineral Industry Surveys HSS 309 by

the Bureau of Mines. These two figures differ largely because the annual canvass of the Bituminous Coal Division includes only mines with 1,000 tons or more yearly production, whereas the Bureau of Mines canvass is concerned with the production of all mines in which men are employed and hence are exposed to accident hazards incident to mining.

SALIENT STATISTICS

TABLE 1.—Salient statistics of the bituminous-coal and lignite industry in the United States, 1940-42

[All tonnage figures represent net tons]

	1940	1 <del>94</del> 1	1942 (preliminary)
Production	460, 771, 500	514, 149, 245	580, 000, 000
Consumption in the United States 1	431, 331, 000	492, 445, 000	540, 726, 000
Stocks at end of year:			
Industrial consumers and retail yards	50, 998, 000	62, 737, 000	85, 889, 000
Stocks on upper Lake docks	6, 998, 258	7, 777, 446	6, 358, 825
Unbilled loads, at mines or in classification yards 2	1, 298, 300	919, 700	139, 700
Price indicators (average per net ton):	<b>A1</b> 00	40.00	00.10
Average cost of railroad fuel purchased, f. o. b. mines 3	\$1.88	\$2.02	\$2.13
Average cost of coking coal at merchant byproduct ovens 4.	\$4.40	\$4. 69 \$9. 15	\$4. 97 \$9. 53
Average retail price—38 cities 5	\$8. 60 \$2. 22	\$9. 15 \$2. 22	\$9. 55 \$2. 31
Average railroad freight charge per net ton 6	<b>\$4.44</b>	\$2, 22	\$2. 31
Underground loading machinery sold:	233	367	352
Mobile loading machines (number)	233 36	907	15
Conveyors, including those with duckbills (units)	1,573	1,800	8 1, 167
Pit-car loaders (units)	1,010	1, 500	1,100
Average number of men employed at mines operating 9	439, 075	456, 981	460,000
Fuel-efficiency indicators:	200,010	100,001	100,000
Pounds of coal per kwhr. at electric power plants 10	1.35	1.34	1.34
Pounds per 1,000 gross ton-miles—railroads 11	113	111	111

<sup>1</sup> Represents certain classes of consumers only. See table 4 for consumers included.

• Bureau of Labor Statistics.
 § Average receipts per net ton of revenue bituminous coal and lignite originated, as reported by the Interstate Commerce Commission,
 ? Young, W. I., Anderson, R. L., Lamb, G. A., and Buch, J. W., Mechanization Sales: Coal Age, February 1943, pp. 86–88; and Min. Cong. Jour., February 1943, pp. 68–70.
 § Not comparable with previous years; in 1942, loading heads were not counted as a separate unit.
 § The figures for 1940 and 1941 are based upon reports of mine operators producing over 1.000 tons. The figure for 1942 is estimated from various sources, including the employment index of the Bureau of Labor Statistics.

Federal Power Commission.
 Interstate Commerce Commission; includes coal equivalent of fuel oil consumed.

## PRODUCTION BY WEEKS AND MONTHS

The following tables summarize the preliminary statistics of weekly and monthly production of bituminous coal and lignite in 1942. The figures are estimates based upon daily and weekly statements of cars of coal and beehive coke loaded by the principal railroads and of shipments over the more important originating rivers. Allowance has been made for commercial truck shipments, local sales, and colliery fuel. The estimates given are based upon the latest information available and differ in some instances from the current figures previously published in the Bituminous Coal Division's Weekly Coal

For the method used in counting holidays, see the chapter on Coal

in Mineral Resources of the United States, 1930, p. 631.

Association of American Railroads.


Intersta te Commerce Commission (class I steam railways, including class I switching and terminal companies)

Excludes freight charges.

As reported by coke operators to the Bureau of Mines.

Bureau of Labor Statistics.

Average receivity not not forwapus bituminous coel and lignite originated as reported by the Inter-



FIEURE 3.—Trends of bituminous coal and lignite production, realization, mine capacity, and net income or deficit in the United States, 1900-1942.

Table 2.—Estimated weekly production of bituminous coal and lignite in the United States in 1942

Week ended-	Production (net tons)	Num- ber of work- ing days	Average net tons per working day	Week ended—	Production (net tons)	Num- ber of work- ing days	Average net tons per working day
Jan. 3	1 3, 726, 000	12	22, 021, 000	July 18	11, 139, 000	6	1, 857, 000
Jan. 10		6	1, 871, 000	July 25	11, 055, 000	6	1, 843, 000
Jan. 17	11, 507, 000	6	1, 918, 000	Aug. 1		6	1, 872, 000
Jan. 24	11, 332, 000	6	1, 889, 000	Aug. 8		6	1, 848, 000
Jan. 31	11, 240, 000	6	1, 873, 000	Aug. 15		6	1, 896, 000
Feb. 7	10, 912, 000	6	1, 819, 000	Aug. 22		6	1, 844, 000
Feb. 14	11, 039, 000	6	1,840,000	Aug. 29	11, 505, 000	-6	1, 918, 000
Feb. 21	10, 971, 000	6	1, 829, 000	Sept. 5	11, 453, 000	6	1,909,000
Feb. 28	11, 452, 000	6	1, 909, 000	Sept. 12	10, 683, 000	5	2, 137, 000
Mar. 7	10, 263, 000	6	1, 711, 000	Sept. 19	11, 704, 000	6	1,951,000
Mar. 14	11, 049, 000	6	1, 842, 000	Sept. 26	11, 577, 000	6	1, 930, 000
Mar. 21	11, 075, 000	6	1, 846, 000	Oct. 3	11, 604, 000	6	1, 934, 000
Mar. 28	11, 311, 000	6	1, 885, 000	Oct. 10	11, 658, 000	6	1, 943, 000
Apr. 4		5. 2	2,011,000	Oct. 17		6	1, 926, 000
Apr. 11	11, 112, 000	6	1, 852, 000	Oct. 24		6	1, 925, 000
Apr. 18	11, 327, 000	6	1, 888, 000	Oct. 31		6	1, 963, 000
Apr. 25	11, 335, 000	6	1, 889, 000	Nov. 7	11, 379, 000	6	1,897,000
May 2	11, 134, 000	6	1, 856, 000	Nov. 14	11, 453, 000	5.7	2,009,000
May 9	11, 271, 000	6	1, 879, 000	Nov. 21	11, 721, 000	6	1, 954, 000
May 16	11, 329, 000	6	1, 888, 000	Nov. 28,	10, 866, 000	5	2, 173, 000
May 23	11, 266, 000	6	1, 878, 000	Dec. 5	11, 331, 000	6	1, 889, 000
May 30	11, 058, 000	5. 3	2, 086, 000	Dec. 12	12, 031, 000	6	2,005,000
June 6		6	1, 839, 000	Dec. 19	11, 815, 000	6	1, 969, 000
June 13		6	1,867,000	Dec. 26	8, 738, 000	5	1, 748, 000
June 20	11,006,000	6	1, 834, 000	Jan. 2, 1943	1 7, 735, 000	14	21, 896, 000
June 27	11, 328, 000	6	1, 888, 000	1			
July 4	8, 172, 000	4	2, 043, 000		580, 000, 000	305. 2	1,900,000
July 11	10, 779, 000	6	1, 797, 000	l			

<sup>&</sup>lt;sup>1</sup> Figures represent output and number of working days in that part of the week included in the calendar year shown. Total production for the week of Jan. 2, 1943, was 9,479,000 net tons, and for the week of Jan. 3, 1942, 10,104,000 net tons.

<sup>2</sup> A verage daily production for the entire week and not for the working days in the calendar year shown.

## TABLE 3.—Estimated monthly production of coal in the United States, by States, in thousands of net tons, in 1942

[Bituminous and lignite figures are preliminary estimates based upon railroad carloadings and river shipments of coal and beehive coke, supplemented by direct reports from a number of mining companies, local coal operators' associations, and detailed monthly production statistics compiled by the State Mine Departments of Colorado, Illinois, Pennsylvania, Washington, and West Virginia. In making the estimates, allowance is made for commercial truck shipments, local sales, and colliery fuel, and for small trucking mines producing over 1,000 tons a year. Where a mine is on the border between two States, the production is accredited to the State from which the coal is extracted, rather than the State in which the tipple is located. The estimates here given differ in a few cases from the current figures previously published in the Weekly Coal Reports]

State	January	February	March	April	Мау	June	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total
Alabama Alaska Arkansas and Oklahoma Colorado Georgia and North Carolina	1, 575 25 422 866 3	1, 460 22 271 715 3	1,608 23 211 685	1, 614 24 223 515 4	1, 610 21 290 550 4	1, 625 22 344 514 3	1, 590 22 386 507 4	1, 560 22 375 596 4	1, 583 23 410 695 4	1, 616 25 427 750 4	1, 454 24 380 752	1, 575 27 407 845 4	18, 870 280 4, 146 7, 990 44
Illinois Indiana Indiana Kansas and Missouri Kentucky:	5, 852	5, 340	5, 250	4, 925	4, 983	5, 124	4, 820	4, 850	5, 455	5, 900	5, 290	5, 961	63, 750
	2, 440	2, 166	2, 160	1, 964	1, 855	1, 625	2, 090	2, 012	2, 215	2, 330	2, 220	2, 393	25, 470
	348	308	268	218	180	185	190	182	214	290	296	311	2, 990
	861	684	676	607	623	590	636	718	726	755	703	761	8, 340
Eastern Western Maryland Michigan Montana (bituminous and lignite)	3, 588	3, 120	3, 517	4, 164	4, 230	4, 105	3, 921	4, 042	4, 110	4, 204	3, 930	3, 796	46, 727
	1, 210	1, 108	1, 045	935	1, 005	1, 058	978	985	1, 145	1, 302	1, 197	1, 272	13, 240
	168	157	175	187	175	175	162	158	146	149	126	120	1, 898
	44	39	29	19	20	22	16	18	27	27	26	33	320
	365	257	300	258	213	244	293	322	356	412	388	450	3, 858
Montana (ottuminous and lighte) New Maxico North and South Dakota (lighte) Ohio Pennsylvania (bituminous)	155 270 2, 745 11, 973	123 219 2, 580 11, 360	138 172 2, 920 12, 365	125 134 2, 970 12, 202	125 100 2, 920 12, 074	137 97 3, 140 12, 285	143 89 2, 952 12, 118	144 107 2, 940 11, 945	150 219 2, 910 12, 068	367 3, 100 12, 326	143 374 2, 753 11, 010	151 340 2, 670 11, 448	1, 696 2, 488 34, 600 143, 174
Tennessee Texas (bituminous and lignite) Utah Virginia	526 28 547 1,736 193	581 21 376 1,396	644 22 434 1,520	664 22 364 1, 762 182	652 24 433 1, 755 171	652 27 482 1,718	611 36 480 1,720 150	620 34 502 1,595 144	636 35 495 1,733 171	655 33 520 1, 764 166	596 32 493 1,614 150	588 28 544 1,587	7, 425 342 5, 670 19, 900 1, 988
Washington West Virginia Wyoming Other Western States	12, 338	11, 308	12, 855	13, 714	13, 296	13, 334	13, 357	13, 320	13, 587	13, 674	12, 720	13, 247	156, 750
	752	592	610	535	550	540	560	655	728	831	797	875	8, 025
	2	2	2	1	1	1	1	1	2	2	2	2	19
Total bituminous coal and lignite Pennsylvania anthracite 1	49, 032	44, 374	47, 796	48, 332	47, 860	48, 220	47, 832	47, 851	49, 843	51, 791	47, 474	49, 595	580, 000
	4, 532	4, 772	5, 085	5, 153	4, 843	5, 122	5, 341	5, 180	5, 426	5, 101	4, 795	4, 611	59, 961
	53, 564	49, 146	52, 881	53, 485	52, 703	53, 342	53, 173	53, 031	55, 269	56, 892	52, 269	54, 206	639, 961

<sup>1</sup> Pennsylvania anthracite figures from Bureau of Mines and subject to revision. Includes Sullivan County, washery and dredge coal, local sales, colliery fuel, and coal shipped by truck from authorized operations.

#### CONSUMPTION

Table 4.—Consumption of bituminous coal and lignite, by consumer class, with retail deliveries in the United States, 1934-42, in thousands of net tons 1

Year	Col- liery fuel	Elec- tric power util- ities 1	Rail- roads (class I) <sup>8</sup>	Bee- hive ovens	By- prod- uct ovens	Steel and rolling mills	Coal- gas retorts	Cement mills 4	Other indus-trials \$	Retail- dealer de- liveries	Total of classes shown
1934 1935 1936 1937 1938 1939 1940 1941	3. 175 3, 103 3, 227 3, 052 2, 493 2, 565 2, 443 2, 489 2, 807	31, 835 33, 013 40, 029 42, 871 38, 245 43, 979 50, 973 61, 861 65, 634	76, 037 77, 109 86, 391 88, 080 73, 921 79, 072 85, 130 97, 384 115, 410	1. 635 1, 469 2. 698 4, 927 1, 360 2, 298 4, 803 10, 529 12, 907	14, 343 49, 046 63, 244 69, 575 45, 266 61, 216 76, 583 82, 609 88, 014	10, 898 11, 747 13, 471 12, 853 8, 412 9, 808 10, 040 10, 902 10, 434	2. 475 2, 245 1, 945 1, 680 1, 644 1, 614 1, 746 1, 659 1, 721	3. 500 3. 516 4 771 5, 247 4. 483 5, 274 3, 633 6, 832 7, 499	83, 793 91, 589 108, 620 122, 410 92, 390 98, 900 106, 280 120, 720 131, 550	86 925 83, 990 84, 200 80, 076 68, 520 71, 570 87, 700 97, 460 104, 750	344, 621 356, 827 408, 596 430, 771 336, 734 376, 296 431, 331 492, 445 540, 726

<sup>1</sup> These data have been assembled to show changes in consumption of bituminous coal and lignite by such classes of consumers as report currently. The total, including retail deliveries, does not represent grand total consumption in the United States. Bunker-fuel statistics are not available for publication at present. The "total of classes shown" for each year in the above table cannot be reconciled with the calculated consumption obtained by the formula: "Production plus imports minus exports plus or minus net changes in consumers' stocks" due to the omission of bunker fuel: to revisions in data covering production, exports, and imports; and to unavoidable irregularities that occur in reports from respondents who are unable to require that definitions applied and closing dates observed by their accountants are identical with those generally used in the surveys of bituminous-coal and lignite consumption.

2 Geological Survey and Federal Power Commission. Represents bituminous coal and lignite consumed by public utility power plants in power generation, including a small quantity of coke amounting to approximately 100,000 tons annually.

3 Association of American Railroads. Represents the consumption of bituminous coal and lignite by class I railways for all uses, including locomotive, powerhouse, shop, and station fuel. The Interstate Commerce

<sup>3</sup> Association of American Railroads. Represents the consumption of bituminous coal and lignite by class I railways for all uses, including locomotive, powerhouse, shop, and station fuel. The Interstate Commerce Commission reports that in 1941 the consumption for all uses by class I line-haul railways plus the purchases for class II and class III railways, plus purchases by all switching and terminal companies combined, was 103,223,446 net tons of bituminous coal and lignite. Similar data from the Interstate Commerce Commission are not yet available for 1942.

<sup>4</sup> Bureau of Mines.

<sup>6</sup> Estimates based uncer secrets.

<sup>5</sup> Estimates based upon reports collected jointly by the National Association of Purchasing Agents and the Bituminous Coal Division from a selected list of representative manufacturing plants. 6 Subject to revision.

## FUEL EFFICIENCY

Table 5.—Indicators of effect of fuel economy on consumption of coal in the United States per unit of performance since the World War of 1914–18

	Pounds	Reduction from base period (percent)
Steam railroads: Pounds per 1,000 gross ton-miles freight service:		
A verage: 1919-20 1941 1942 Pounds per passenger-train car-mile:	170 111 111	34. 7 34. 7
Average: 1919-20 1941 1942 Electric public utility power plants: Pounds per kilowatt-hour:	18. 5 14. 9 15. 1	19. 5 18. 4
1919 1941 1942 Iron and steel—pounds coking coal per net ton of pig; <sup>1</sup>	3. 2 1. 3 1. 3	59. 4 59. 4
1918	3, 194 2, 525 2, 604	20. 9 18. 5
oils, and breeze by extension of byproduct in place of beehive coking, 1913-42, expressed as percent of coal used for all coke in 1942?		18. 5

<sup>&</sup>lt;sup>1</sup> Includes only savings through higher yields of merchantable coke per ton of coal charged and lower consumption of coke per ton of iron. Excludes economies through recovery of byproducts, which are

covered in next item.

2 These byproducts are used in part for boiler fuel, in part for metallurgical purposes, in part for domestic heating and coking, and to a small extent for automotive fuel.

というべつからいか ある はばれていている かんしょう

THE REPORT OF THE PARTY OF THE




FIGURE 4.—Trends of fuel efficiency in the United States, 1915-42.

## RELATIVE RATE OF GROWTH OF COAL, OIL, AND WATER POWER, 1889-1942

According to preliminary data, the total supply of available energy in the form of coal, oil, natural gas, and water power in 1942 was 31,785 trillion B. t. u.—an 8.7-percent increase over 1941 (see fig. 5).

The figures are expressed in British thermal units because some common denominator is necessary for such unlike quantities as tons of coal, barrels of oil, and cubic feet of gas. Table 6 summarizes the equivalent of each of the fuels in trillions of British thermal units. Water power is represented by the equivalent fuel required to perform the same work. The table covers the years since 1933. Details for 1889 to 1932 are given in Minerals Yearbook, 1937, page 807.

In converting water power to its fuel equivalent, two alternative assumptions have been made. The first, as in previous issues of these tables, assumes a constant fuel equivalent of 4.02 pounds of coal for each kilowatt-hour of water power produced throughout the entire period from 1889 to 1942. This factor was selected because it represents, in round numbers, the average efficiency of all central stations generating steam-electric power in 1913, the midpoint of the period under review. The usefulness of the constant factor lies in showing the rate at which water power is being developed. It permits direct comparison between the relative increase (in kilowatt-hours of water power) and the corresponding increase or decrease (in tons of coal, barrels of oil, or cubic feet of gas produced). On the other hand, the constant factor makes no allowance for the fact that coal and other fuels produced today are used more efficiently than formerly.

To throw light on the influence of improving fuel efficiency, a second computation of the energy equivalent of water power has therefore This assumes a prevailing fuel equivalent, diminishing been made. year by year, which represents the average performance of all fuelburning central electric stations for the year in question. average has declined from about 7.05 pounds of coal per kilowatt-hour in 1899 to 1.34 pounds in 1942. (The prevailing factor is thus much above the constant factor in 1899 and much below it in 1942.) The prevailing fuel equivalent indicates more nearly the quantity of fuel that would have been needed in any one year to generate the same power in a steam-electric station. It should be noted, however, that the ultimate uses to which the water power generated is put often displace fuel burned much less efficiently than in central stations and that in any instance no other important branch of fuel consumption has made advances in fuel efficiency approaching that of the central stations.

As these tables attempt to determine the total energy from all fuels and from water power, the ideal factor for converting water power into fuel equivalent would be the average efficiency of all forms of fuel consumption in each year. No basis for determining such an all-embracing average exists at present, but enough is known to make certain that it would show much less reduction from 1899 to 1942 than did the central stations. For the present, a just comparison of the changing contributions of water power and of fuel to the national energy supply would lie somewhere between the results shown by the constant equivalent and the prevailing central-station equivalent in

these tables.

As in earlier issues of these tables, the figures for oil and natural gas represent the entire production of crude petroleum and of gas. Most of this production does not come into direct competition with Much of the supply of both oil and gas is used in regions of the country, such as California and portions of the Southwest, where coal is available only at unusually high cost because of heavy transport charges. Nearly half of the natural gas is used in the field for drilling or operating oil and gas wells and pipe lines or for the manufacture of More than half the oil is used in the form of gasoline. carbon black. kerosine, and lubricants, for which purposes coal cannot well compete, except at very much higher levels of oil prices. Even these refined products, however, involve a certain measure of indirect competition with coal, for the energy market of the country is becoming more fluid and competitive and a demand that cannot be met by one source of supply tends to fall back on the others.

The subject of interfuel competition is exceedingly complex, and an elaborate analysis and the accumulation of data not now available would be required to determine even approximately how much of any one fuel actually has been displaced either by other fuels or by water The present tables do not permit determination of such displacement; their purpose is rather to measure the long-time trends in

the total demand for energy.




FIGURE 5.—Annual supply of energy from mineral fuels and water power in the United States, 1889-1942.




FIGURE 6.—Percentage of total B. t. u. equivalent contributed by the several sources of energy in the United States, counting water power at constant fuel equivalent, 1889-1942. If water power is counted at the prevailing fuel equivalent of central stations in each year, its proportion 3.2 percent in 1899 and 3.9 percent in 1942, and the proportions of the other sources of energy are affected accordingly.

TABLE 6.—Annual supply of energy from mineral fuels and water power in the United States, 1933-42,1 in trillions of B. t. u.2

		Coal		Petro (total dinclu that re	crude, ding	Natu-	Total		(fuel e	power quiva- ıt)	Grand ene	l total rgy
Year	Penn- syl- vania an- thra- cite	Bitu- minous coal and lignite	Total	Do- mestic pro- duc- tion	Im- ports	ral gas (total pro- duc- tion)	petro- leum and natu- ral gas	Total mineral fuels	At constant fuel equivalent 3	At prevailing central station equivalent 4	Water power at con- stant fuel equiv- alent	Water power at pre- vailing central station equiv- alent
1933	1, 348 1, 555 1, 419 1, 485 1, 410 1, 255 1, 400 1, 400 1, 533 1, 631	8, 741 9, 415 9, 756 11, 504 11, 673 9, 132 10, 345 12, 072 13, 471 15, 196	10, 089 10, 970 11, 175 12, 989 13, 083 10, 387 11, 745 13, 472 15, 004 16, 827	5, 434 5, 448 5, 980 6, 598 7, 675 7, 286 7, 590 8, 119 8, 413 8, 313	191 213 193 194 165 158 199 256 (6)	1, 672 1, 904 2, 060 2, 330 2, 588 2, 468 2, 663 2, 860 3, 024 3, 171	7, 297 7, 565 8, 233 9, 122 10, 428 9, 912 10, 452 11, 235 611, 437 611, 484	17, 386 18, 535 19, 408 22, 111 23, 511 20, 299 22, 197 24, 707 6 26, 441 6 28, 311	1, 931 1, 896 2, 207 2, 256 2, 446 2, 466 2, 423 2, 620 2, 804 3, 474	711 698 806 812 871 866 838 880 934 1,157	19, 317 20, 431 21, 615 24, 367 25, 957 22, 765 24, 620 27, 327 6 29, 245 6 31, 785	18, 097 19, 233 20, 214 22, 923 24, 382 21, 165 23, 035 25, 587 6 27, 375 6 29, 468

6 Excludes imports of crude petroleum. Figures not available for publication.

TABLE 7.—Index numbers for relative rate of growth of coal, oil, and water power in the United States, 1933-421

[The figures are expressed as a percentage of the 1918 rate]

		Coal			eleum erude)				Water	Grand	l total
Year	Penn- syl- vania anthra- cite	Bitu- minous coal and lignite	Total	Domes- tic produc- tion	Im- ports	Natural gas' (total produc- tion)	leum	Total min- eral fuels	power (at con- stant fuel equiva- lent)	With water power at constant fuel equivalent	With water power at pre- vailing central station equiva- lent
1933	50 58 53 55 52 47 52 52 52 57 61	57 62 64 76 77 60 68 80 89	56 61 63 73 73 58 66 75 84 94	252 255 280 309 359 341 335 380 394 389	90 94 85 86 73 70 88 113 (3)	205 246 266 301 334 318 344 369 390 409	229 241 262 291 332 316 333 358 3 365 3 366	82 88 92 105 112 97 106 118 3 126 3 135	231 227 264 270 292 295 289 313 335 415	87 94 99 112 119 104 113 125 3 134 3 146	83 89 93 106 112 98 106 118 3 126 3 136

<sup>&</sup>lt;sup>1</sup> Comparable data for earlier years in Minerals Yearbook, 1937, p. 809.

¹ Comparable data for earlier years in Minerals Yearbook, 1937, p. 807.
² The unit heat values employed are: Anthracite, 13,600 B. t. u. per pound; bituminous coal and lignite, 13,100 B. t. u. per pound; petroleum, 6,000,000 B. t. u. per barrel; natural gas, 1,075 B. t. u. per cubic foot. Water power includes installations owned by manufacturing plants and mines, as well as Government and privately owned public utilities. The fuel equivalent of water power is calculated from the kilowatt-hours of power produced wherever available, as is true of all public utility plants since 1919. Otherwise the fuel equivalent is calculated from the reported horsepower of installed water wheels, assuming a capacity factor of 20 percent for manufacturers and mines and of 40 percent for public utilities.
³ Assuming 4.02 pounds per kilowatt-hour, which is average of central-electric-station practice in 1913, the base period used.
⁴ Assuming the average central-station practice for each of the years for which data are available, which declined from about 7.05 pounds per kilowatt-hour in 1899 to 1.34 pounds in 1942.
⁵ Subject to revision.

<sup>Subject to revision.
Excludes imports of crude petroleum. Figures not available for publication.</sup> 

Table 8.—Percentage of total B. t. u. equivalent contributed by the several mineral fuels and water power in the United States, 1933-42 \(^1\)

		Coal			oleum crude)	Natural gas	Total petro-	Total	Water power.	Grand total,
Year	Penn- sylvania anthra- cite	Bitu- minous coal and lignite	Total	Domes- tic pro- duction	Imports	(total produc- tion)	leum and natural gas	mineral fuels	fuel equiva- lent	includ- ing water power
	Water	power co	unted at	constant fi	iel equiva	lent of ap	proximate	ly 4 lb. p	er kilowat	t-hour
1933	7.0 7.6 6.6 6.1 5.4 5.5 5.7 5.1 5.2	45. 2 46. 1 45. 1 47. 2 45. 0 40. 1 42. 0 44. 2 46. 1 47. 8	52. 2 53. 7 51. 7 53. 3 50. 4 45. 6 47. 7 49. 3 51. 3 52. 9	28. 1 26. 7 27. 7 27. 1 29. 6 32. 0 30. 8 29. 7 28. 8 26. 2	1.0 1.0 .9 .8 .6 .7 .8 .9	8.7 9.3 9.5 9.5 10.0 10.8 10.8 10.5 10.3 10.0	37.8 37.0 38.1 37.4 40.2 43.5 42.4 41.1 39.1 36.2	90. 0 90. 7 89. 8 90. 7 90. 6 89. 1 90. 1 90. 4 90. 4 89. 1	10. 0 9. 3 10. 2 9. 3 9. 4 10. 9 9. 9 9. 6 9. 6 10. 9	100.0 100.0 100.0 100.0 100.0 100.0 100.0 100.0 100.0
		Wate	r power c	ounted at	prevailing	central-s	tation equ	ivalent fo	r year	
1933 1934 1935 1936 1937 1938 1939 1940 1941 2 1942 2	7. 4 8. 1 7. 0 6. 5 5. 8 5. 9 6. 1 5. 5 5. 6 5. 5	48. 4 49. 0 48. 3 50. 2 47. 8 43. 2 44. 9 47. 2 49. 2 51. 6	55. 8 57. 1 55. 3 56. 7 53. 6 49. 1 51. 0 52. 7 54. 8 57. 1	30. 0 28. 3 29. 5 28. 8 31. 5 34. 4 32. 9 31. 7 30. 7 28. 2	1.1 1.1 1.0 .8 .7 .7 .9 1.0 (3)	9, 2 9, 9 10, 2 10, 2 10, 6 11, 7 11, 6 11, 2 11, 1 10, 8	40. 3 39. 3 40. 7 39. 8 42. 8 46. 8 45. 4 43. 9 41. 8 39. 0	96. 1 96. 4 96. 0 96. 5 96. 4 95. 9 96. 4 96. 6 96. 6	3. 9 3. 6 4. 0 3. 5 3. 6 4. 1 3. 6 3. 4 3. 4 3. 9	100. 0 100. 0 100. 0 100. 0 100. 0 100. 0 100. 0 100. 0

Comparable data for earlier years in Minerals Yearbook, 1937, p. 810.
 Subject to revision. Percentages based upon figures in table 6.
 Figures not available for publication.

# DISTRIBUTION Table 9.—Trends in distribution of bituminous coal and lignite in the United States, 1937–42

[For details and sources of data, see Monthly Report on Distribution of Coal Shipments. Tonnage figures shown in thousands of net tons]

	19	37	19	938	19	939	19	) <del>4</del> 0	19	41	1942 (pre	liminary)
	M net tons	Percent	M net tons	Percent	M net tons	Percent	M net tons	Percent	M net tons	Percent	M net	Percent
New England receipts: Via rail across the Hudson	4, 885		4, 104		4, 626		4, 892		6, 385		9, 938	
Lake Erie loadings (cargo and fuel): By fields of origin: From Ohlo	3, 231 11, 763	7. 1 26. 0	2, 390 8, 019	6. 8 22. 8	2, 356 9, 259	5. 7 22. 5	2, 646 11, 578	5. 5 24. 1	3, 947 11, 612	7. 7 22. 6	4, 171 9, 305	8. 5 18. 8
Piedmont. From Southern West Virginia: High volatile. Low volatile. From Eastern Kentucky, Tennessee, and Vir-	2, 319 10, 975 8, 428	5. 1 24. 3 18. 6	1, 389 8, 329 7, 612	4. 0 23. 7 21. 7	1, 963 10, 883 8, 665	4. 8 26. 5 21. 1	2, 357 12, 025 10, 372	4. 9 25. 0 21. 6	2, 963 14, 277 9, 010	5. 8 27. 8 17. 5	2, 778 14, 746 9, 160	5. 6 29. 8 18. 5
From Eastern Kentucky, Tennessec, and Virginia	8, 530 45, 246	18. 9	7, 392	21. 0	7, 998	19.4	9, 133	18. 9	9, 585	18. 6	9, 295	18. 8
By destinations (eargo only): To American points. To Canadian points.	35, 123 8, 479	80. 6	27, 656 6, 510	80. 9 19. 1	41, 124 33, 188 6, 672	83. 3 16. 7	48, 111 37, 804 8, 778	81. 2 18. 8	38, 823 10, 886	78. 1 21. 9	49, 455 36, 267 11, 544	75. 9 24. 1
Total Across Lake Michigan car ferry	43, 602 650	100.0	34, 166 588	100. 0	39, 860 592	100. 0	46, 582 612	100.0	49, 709 627	100.0	47, 811 740	100.0
West-bound rail to Mississippi Valley (revenue all- rail shipments, excluding railroad fuel, Lake coal, and movements to Kentucky points): From Ohio fields	11, 861 15, 091 3, 521	9. 5 12. 1 2. 8	8, 042 9, 620 2, 615	8. 7 10. 4 2. 8	9, 052 12, 200 3, 227	8.4 11.4 3.0	9, 807 15, 195 3, 467	8. 0 12. 4 2. 8	10, 846 16, 663 4, 728	7. 9 12. 1 3. 4	11, 719 18, 141 5, 201	7. 4 11. 5 3. 3
From Southern West Virginia: High volatile Low volatile	17, 293 19, 575	13. 9 15. 8	13, 668 13, 335	14. 8 14. 5	15, 099 15, 946	14. 0 14. 8	16, 943 19, 536	13. 8 15. 9	18, 275 22, 773	13. 3 16. 6	21, 500 25, 005	13. 6 15. 9

From Eastern Kentucky, Tennessee, and Vir-			1		1	1	1	1	أحددا				
ginia	17, 953	14.5	14, 120	15. 3	15, 749	14.7	18, 340	14. 9	18, 980	13.8	22, 770	14. 4	
Total from Appalachian fields	85, 294	68. 6	61, 400	66. 5	71, 273	66. 3	83, 288	67. 8	92, 265	67. 1	104, 336	66. 1	
From IllinoisFrom IndianaFrom Western Kentucky	26, 625 10, 594 1, 859	21. 4 8. 5 1. 5	20, 719 8, 501 1, 661	22. 5 9. 2 1. 8	24, 879 9, 455 1, 917	23. 1 8. 8 1. 8	27, 618 10, 223 1, 758	22. 5 8. 3 1. 4	30, 100 12, 499 2, 735	21. 9 9. 0 2. 0	36, 992 14, 031 2, 556	23. 4 8. 9 1. 6	
Total from middle western fields	39, 078	31. 4	30, 881	33. 5	36, 251	33. 7	39, 599	32. 2	45, 334	32. 9	53, 579	33. 9	
Grand total	124, 372	100. 0	92, 281	100. 0	107, 524	100. 0	122, 887	100. 0	137, 599	100.0	157, 915	100. 0	
including, in this case, nonrevenue railroad fuel):  From Michigan fields  From upper Lake commercial docks, all deliver-	181 13, 518	(2 3) 2 3 . 1	166 10, 845	(3 8) 2 3. 1	122 11, 111	(2 3) 2 2.8	103 12, 054	(3 3) 3 2. 6	120 12, 473	(2 3)	71 14, 036	(2 8)	
ies)	7, 202 3, 739 21, 867	<sup>3</sup> 1. 6 <sup>2</sup> . 8 <sup>3</sup> 4. 9	6, 528 3, 126 17, 612	3 1. 9 3. 9 3 5. 1	6, 088 2, 946 18, 442	<sup>2</sup> 1. 5 <sup>2</sup> . 7 <sup>3</sup> 4. 7	6, 411 3, 394 19, 658 14, 288	11.4 2.7 24.3 23.1	6, 731 3, 411 22, 009 14, 310	1.3 1.7 14.3 12.8	8, 147 4, 152 26, 265 17, 777	3 1. 4 3. 7 3 4. 5 3 3. 1	
From Alabama field	11,771	3 2. 7	10, 382	3 3. 0	11, 233	3 2.8	14, 200	- 5.1	14, 510	-2.0	11,111	- 0. 1	

Excluding commercial sales by truck and wagon, except from upper Lake docks.
Percent of total national shipments from all mines, all destinations.
Less than 0.1 percent.




FIGURE 7.—Monthly movement of bitumiaous coal and lignite in the United States in the major channels of distribution, 1941–42.

## STOCKS HELD BY CONSUMERS

Table 10.—Stocks of bituminous coal and lignite in hands of commercial consumers and in retail dealers' yards in the United States, 1941-42

		Da	ys' suppl	y at curr	ent rate	of consun	aption o	n date of	stock tal	ing
Date	Total stock (net tons)	Byprod- uct coke plants	Steel plants	Other indus- trials	Coal-gas plants	Electric utilities	Retail yards	Rail- roads	Cement mills	Total
1941 Jan. 1 Feb. 1 Mar. 1 Apr. 1 May 1 June 1 July 1 Aug. 1 Sept. 1 Oct. 1 Nov. 1 Dec. 1 Dec. 1 Dec. 31	50, 998, 000 48, 702, 000 48, 518, 000 50, 690, 000 35, 971, 000 42, 929, 000 47, 051, 000 52, 801, 000 56, 994, 000 61, 763, 000 62, 737, 000	45 43 43 43 23 21 26 27 31 32 37 36 38	26 28 30 39 23 27 26 27 28 31 32 30 30	42 37 35 38 34 38 45 53 59 61 58 54	51 53 50 51 41 37 53 69 70 79 79	74 72 69 74 65 57 58 62 60 63 62 67 67	28 19 16 14 26 32 32 34 31 33 36 34 27	23 24 26 32 24 25 26 26 28 31 33 34 33	27 81 33 37 24 25 27 27 30 31 34 33 33	38 34 32 35 32 35 38 40 42 43 43
1942 Jan. 1 Feb. 1 Mar. 1 Apr. 1 May 1 June 1 July 1 Aug. 1 Sept. 1 Oct. 1 Nov. 1 Dec. 1 Dec. 31	62, 737, 000 58, 681, 000 56, 885, 000 57, 221, 000 61, 336, 000 73, 271, 000 82, 686, 000 87, 311, 000 90, 374, 000 85, 889, 000	38 34 33 33 35 35 41 41 42 44 45 46 44	30 30 33 33 37 42 45 48 50 48 46 42 34	50 45 42 48 54 69 78 87 94 92 85 80 69	76 72 66 59 63 71 80 96 90 89 89 88 89	67 66 73 86 94 96 98 94 99 105 110 111 101	27 17 15 17 21 26 33 48 53 42 44 45 28	34 31 30 32 35 38 41 44 45 43 41 39	37 36 37 42 43 42 46 49 50 48 47 47	40 34 34 38 43 49 54 60 63 61 61 59

<sup>&</sup>lt;sup>1</sup> Unadjusted for coal in transit during suspension of mining in April 1941.

## FINAL BITUMINOUS-COAL AND LIGNITE STATISTICS FOR 1941

Tables 11 to 45 give the final detailed statistics of bituminous-coal and lignite mine operations in 1941. The subjects covered include production, number and size of mines, employment, value, mechanization, and world production.

In accordance with the practice followed by the Bureau of Mines in previous years, the statistics in this report relate to mines having an




FIGURE 8.—Trends of employment, mechanization, and output per man at bituminous-coal and lignite mines in the United States, 1900-1941.

output of 1,000 tons a year or more and do not attempt to include many small mines producing less than 1,000 tons a year that sell their output by wagon or truck.

These statistics include, for convenience and historical comparison, the small output of anthracite and semianthracite produced outside

Pennsylvania and the production of lignite.

## SALIENT TRENDS

Table 11.—Growth of bituminous-coal and lignite mining industry in the United States, 1890–1941

vije sel			Value	Men em-	Number	Calculated	d capacity of net tons)	(millions
Year	Production	Value <sup>1</sup>	per ton i	ployed	of mines	At 308 days	At 280 days	At 261 days
890 891 892 893	111, 302, 322 117, 901, 238 126, 856, 567 128, 385, 231 118, 820, 405	\$110, 420, 801 117, 188, 400 125, 124, 381 122, 751, 618 107, 653, 501	\$0.99 .99 .99 .96	192, 204 205, 803 212, 893 230, 365 244, 603	(2) (2) (2) (2) (3)	152 163 178 194 214	137 148 162 174 196	129 138 151 164 181
895 896 897 898	135, 118, 193 137, 640, 276 147, 617, 519 166, 593, 623 193, 323, 187	115, 779, 771 114, 891, 515 119, 595, 224 132, 608, 713 167, 952, 104	.86 .83 .81 .80 .87	239, 962 244, 171 247, 817 255, 717 271, 027	2, 555 2, 599 2, 454 2, 862 3, 245	215 221 232 243 254	196 202 213 221 230	182 187 197 206 216
900 901 902 903 904	212, 316, 112 225, 828, 149 260, 216, 844 282, 749, 348 278, 659, 689	220, 930, 313 236, 422, 049 290, 858, 483 351, 687, 933 305, 397, 001	1.04 1.05 1.12 1.24 1.10	304, 375 340, 235 370, 056 415, 777 437, 832	(2) (2) (2) (2) (2) 4, 650	279 309 348 387 425	255 281 316 350 386	237 262 293 328 360
905 906 907 908	315, 062, 785 342, 874, 867 394, 759, 112 332, 573, 944 379, 744, 257	334, 658, 294 381, 162, 115 451, 214, 842 374, 135, 268 405, 486, 777	1.06 1.11 1.14 1.12 1.07	460, 629 478, 425 513, 258 516, 264 543, 152	5, 060 4, 430 4, 550 4, 730 5, 775	460 496 520 531 560	417 451 473 482 510	390 420 440 450 470
910 911 912 913 914	417, 111, 142 405, 907, 059 450, 104, 982 478, 435, 297 422, 703, 970	469, 281, 719 451, 375, 819 517, 983, 445 565, 234, 952 493, 309, 244	1.12 1.11 1.15 1.18 1.17	555. 533 549, 775 548, 632 571, 882 583, 506	5, 818 5, 887 5, 747 5, 776 5, 592	592 593 622 635 668	538 538 566 577 608	50: 50: 52: 53: 56:
915 916 917 918 919		502, 037, 688 665, 116, 077 1, 249, 272, 837 1, 491, 809, 940 1, 160, 616, 013	1. 13 1. 32 2. 26 2. 58 2. 49	557, 456 561, 102 603, 143 615, 305 621, 998	5, 502 5, 726 6, 939 8, 319 8, 994	672 673 699 717 736	610 613 636 650 669	56 57 59 60 62
920	415, 921, 950 422, 268, 099	2, 129, 933, 000 1, 199, 983, 600 1, 274, 820, 000 1, 514, 621, 000 1, 062, 626, 000	3. 75 2. 89 3. 02 2. 68 2. 20	639, 547 663, 754 687, 958 704, 793 619, 604	8, 921 8, 038 9, 299 9, 331 7, 586	796 860 916 970 871	725 781 832 885 792	67 72 77 82 73
925 926 927 928 1929	1 573, 366, 985	1,060,402,000 1,183,412,000 1,029,657,000 933,774,000 952,781,000	2. 04 2. 06 1. 99 1. 86 1. 78	588, 493 593, 647 593, 918 522, 150 502, 993	7, 144 7, 177 7, 011 6, 450 6, 057	822 821 835 760 752	748 747 759 691 679	69 69 70 64 63
1930	1	795, 483, 000 588, 895, 000 406, 677, 000 445, 788, 000 628, 383, 000	1.70 1.54 1.31 1.34 1.75	493, 202 450, 213 406, 380 418, 703 458, 011	5, 891 5, 642 5, 427 5, 555 6, 258	770 736 653 615 622	700 669 594 559 565	65 62 55 52 52
1935 1936 1937 1938	379 373 199	658, 063, 000 770, 955, 000 864, 042, 000 678, 653, 000 728, 348, 366	1.77 1.76 1.94 1.95 1.84	462, 403 477, 204 491, 864 441, 333 421, 788	6, 315 6, 875 6, 548 5, 777 5, 820	640 680 710 663 683	582 618 646 602 621	54 57 60 56 57
1940 1941	460, 771, 500	879, 327, 227 1, 125, 362, 836	1.91 2.19	439, 075 456, 981	6, 324 6, 822	703 733	639 666	59 62

<sup>&</sup>lt;sup>1</sup> Figures on value and value per ton for the years 1890 to 1936, inclusive, and 1939 exclude selling expense. Figures for other years include selling expense. <sup>2</sup> Data not available.

Table 11.—Growth of bituminous-coal and lignite mining industry in the United States, 1890-1941—Continued

	Average number	days lo	number of ost on ac- f strikes	Net tons	per man		of under- roduction	Percent produ	of total action
Year	of days worked	Per man employed	Per man on strike	Per day	Per year	Cut by machines 1	Mechani- cally loaded	Mechani- cally cleaned 2	Mined by stripping
1890 1891 1892 1893 1894	226 223 219 204 171	(3) (3) (3) (3) (3)	(3) (3) (3) (3)	2. 56 2. 57 2. 72 2. 73 2. 84	579 573 596 557 486	(3) 5. 3 (3) (3) (3)	(3) (3) (3) (3) (3)	(3) (3) (3) (3) (3)	(3) (3) (3) (3) (3)
1895 1896 1897 1898 1899	194 192 196 211 234	(3) (3) (3) (3) (3)	(3) (3) (3) (3) (3) 46	2. 90 2. 94 3. 04 3. 09 3. 05	563 564 596 651 713	(3) 11. 9 15. 3 19. 5 22. 7	(3) (3) (3) (3) (3)	(3) (3) (3) (3)	(3) (3) (3) (3) (3)
1900	234	5	43	2. 98	697	24. 9	(3)	(3)	(3)
1901	225	2	35	2. 94	664	25. 6	(3)	(3)	(3)
1902	230	7	44	3. 06	703	26. 8	(3)	(3)	(3)
1903	225	3	28	3. 02	680	27. 6	(3)	(3)	(3)
1904	202	8	44	3. 15	637	28. 2	(3)	(3)	(3)
1905	211	2	23	3. 24	684	32. 8	(3)	(3)	(3)
1906	213	28	63	3. 36	717	34. 7	(3)	2.7	(3)
1907	234	1	14	3. 29	769	35. 1	(3)	2.9	(3)
1908	193	11	38	3. 34	644	37. 0	(3)	3.6	(3)
1909	209	11	29	3. 34	699	37. 5	(3)	3.8	(3)
1910	217	35	89	3. 46	751	41. 7	(3)	3.8	(3)
1911	211	2	27	3. 50	738	43. 9	(3)	(3)	(3)
1912	223	10	35	3. 68	820	46. 8	(3)	3.9	(3)
1913	232	4	36	3. 61	837	50. 7	(3)	4.6	(3)
1914	195	19	80	3. 71	724	51. 8	(3)	4.8	0. 3
1915 1916 1917 1918 1919	203 230 243 249 195	4 4 4 1 25	61 26 17 7 37	3. 91 3. 90 3. 77 3. 78 3. 84	794 896 915 942 749	55. 3 56. 9 56. 1 56. 7 60. 0	(3) (3) (3) (3)	4.7 4.6 4.6 3.8 3.6	.6 .8 1.0 1.4 1.2
1920	220	6	22	4. 00	881	60. 7	(3)	3. 3	1.5
1921	149	3	23	4. 20	627	66. 4	(3)	3. 4	1.2
1922	142	78	117	4. 28	609	64. 8	(3)	(3)	2.4
1923	179	2	20	4. 47	801	68. 3	0.3	3. 8	2.1
1924	171	7	73	4. 56	781	71. 5	.7	(3)	2.8
1925	195	2	30	4. 52	884	72. 9	1, 2	(3)	3. 2
1926	215	1	24	4. 50	966	73. 8	1, 8	(3)	3. 0
1927	191	45	153	4. 55	872	74. 9	(3)	5. 3	3. 6
1928	203	8	83	4. 73	959	76. 9	4, 5	5. 7	4. 0
1929	219	(4)	11	4. 85	1,064	78. 4	7, 4	6. 9	3. 8
1930	187	2	43	5. 06	948	81. 0	10. 5	8.3	4. 3
1931	160	3	35	5. 30	849	83. 2	13. 1	9.5	5. 0
1932	146	19	120	5. 22	762	84. 1	12. 3	9.8	6. 3
1933	167	9	30	4. 78	797	84. 7	12. 0	10.4	5. 5
1934	178	3	15	4. 40	785	84. 1	12. 2	11.1	5. 8
1935	179	(3)	(3)	4. 50	805	84. 2	13. 5	12. 2	6. 4
1936	199	2	21	4. 62	920	84. 8	16. 3	13. 9	6. 4
1937	193	(3)	(3)	4. 69	906	(3)	20. 2	14. 6	7. 1
1938	162	1	13	4. 89	790	87. 5	26. 7	18. 2	8. 7
1939	178	25	36	5. 25	936	87. 9	31. 0	20. 1	9. 6
1940	202	· 1 20	8	5. 19	1, 049	88. 4	35. 4	22. 2	9. 4
1941	216		27	5. 20	1, 125	89. 0	40. 7	22. 9	10. 7

Percentages for the years 1890 to 1913, inclusive, are of total production, as a separation of strip mine and underground production is not available for these years.
 For the years 1906 to 1926, inclusive, these percentages are exclusive of coal cleaned at central washeries operated by consumers; after 1926, when data became available on the tonnage cleaned by consumer-operated plants, the percentages include the total tons cleaned at the mines and at consumer-operated washeries.
 Data not available.
 One-half day or less.

Table 12.—Salient trends in bituminous-coal and lignite mining industry in the United States, 1934-41

THE IZ. Salvett Works to								
	1934	1935	1936	1937	1938	1939	1940	1941
Production: Loaded at mine for shipment by rail	313, 303, 729 15, 127, 968 18, 739, 320 (2) (2) 2 7, 374, 143 3, 175, 057 1, 647, 805	319, 741, 376 18, 327, 282 21, 960, 252 (3) (3) 2 7, 773, 619 3, 102, 691 1, 467, 902	370, 762, 901 24, 867, 683 27, 929, 298 (*) (3) * 9, 571, 997 3, 227, 447 2, 728, 577	1 399, 237, 575 (1) 2 37, 762, 612 (2) (2) (2) (2) (3) (4) 3, 052, 095 4, 884, 054	295, 336, 027 16, 902, 969 25, 592, 058 606, 857 4, 221, 671 2, 032, 289 2, 493, 017 1, 359, 876	331, 189, 620 22, 229, 364 29, 533, 824 826, 536 4, 317, 465 1, 901, 408 2, 565, 276 2, 089, 475	380, 387, 674 29, 493, 058 35, 540, 476 939, 058 5, 887, 994 2, 035, 201 2, 442, 989 4, 045, 050	425, 184, 319 30, 240, 489 40, 055, 638 1, 099, 582 6, 067, 697 1, 872, 026 2, 488, 950 7, 140, 544
Total productiondo	359, 368, 022	372, 373, 122	439, 087, 903	4 445, 531, 449	348, 544, 764	<sup>8</sup> 394, 855, 325	460, 771, 500	514, 149, 245
Number of active mines of commercial size: Class 1 (200,000 tons or more) Class 2 (100,000 to 200,000 tons) Class 3 (50,000 to 100,000 tons) Class 4 (10,000 to 50,000 tons) Class 5 (1,000 to 10,000 tons)	485	561 479 503 1,056 3,716	660 452 460 1,085 4,218	661 469 448 1,117 3,853	526 402 415 1,042 3,392	577 404 387 1,065 3,387	636 432 371 1, 157 3, 728	730 437 402 1, 305 3, 948
Total number over 1,000 tons	6, 258	6, 315	6, 875	6, 548	5, 777	5, 820	6, 324	6, 822
Average number of men employed at mines active: Underground Surface: In strip pits All others	384, 947 7, 652 65, 412	389, 942 8, 533 63, 928	399, 367 8, 043 69, 794	(6) (6)	370, 004 7, 877 63, 452	353, 476 8, 791 59, 521	365, 013 8, 983 65, 079	376, 765 10, 861 69, 355
Total.  A verage number of days mines operated. Capacity of active mines with existing labor force: Per year of 308 days	458, 011 178 622, 000, 000 565, 000, 000 527, 000, 000 4, 40 785 284, 676, 715 84, 1 41, 432, 735 12, 2 20, 789, 641 5, 8 39, 826, 559	462, 403 179 640,000,000 582,000,000 4,50 805 293, 664, 208 84, 2 47, 177, 224 113, 5 23, 647, 292 6,4 45, 361, 021	477, 204 199 680, 000, 000 618, 000, 000 576, 000, 000 4. 62 920 348, 332, 330 84. 8 66, 976, 872 16. 3 28, 125, 857 6. 4 61, 094, 976	491, 864 193 710, 000, 000 646, 000, 000 601, 000, 000 4, 69 906 (e) 83, 500, 000 31, 750, 853 7, 1 65, 000, 000	441, 333 162 663, 000, 000 602, 000, 000 562, 000, 000 4, 89 278, 315, 365 87, 5 85, 092, 836 87, 5 80, 406, 855 8, 7 63, 454, 588	421, 788 178 683, 000, 000 621, 000, 000 579, 000, 000 5, 25 936 313, 969, 394 87, 9 110, 711, 970 37, 722, 583 9, 6	439, 075 202 703, 000, 000 639, 000, 000 595, 000, 000 1, 049 369, 227, 277 4147, 870, 252 43, 167, 336 9, 4 102, 205, 188	456, 981 218 733, 000, 000 666, 000, 000 621, 000, 000 5, 20 1, 125 408, 510, 296 89, 0 186, 667, 250 40, 7 55, 071, 609 10, 7 117, 469, 857
Percent of underground output mechanically loadednet tonsnet tons	12. 2 20, 789, 641	13. 5 23, 647, 292	16. 3 28, 125, 857	20. 2 31, 750, 853 7. 1	26. 7 30, 406, 855 8. 7	31. 0 37, 722, 583 9. 6	35. 4 43, 167, 336 9. 4	55, 07

- In 1937, coal loaded at mine for shipment by water is included with "loaded at mine for shipment by rail."
  In 1937, coal "taken by locomotive tenders at tipple," "shipped by conveyor or tram to point of consumption," and "used by mine employees" included with "shipped by truck or wagon."
  In 1934, 1935, and 1936, data were not collected in such form as to permit a separation of coal "taken by locomotive tenders at tipple," "shipped by conveyor or tram to point of consumption," and "used by mine employees." They are all included here under "used by mine employees."
  Total production differs from sum of items shown by amount of changes in inventory and tonnage not accounted for in distribution analysis. This tonnage amounted to 595,113
- - 8 Includes 202,337 tons of coal reported as net changes in stocks at mines, January 1, 1939, to January 1, 1940.

  - Data not available.
    Includes central washeries operated by consumers.

Table 13.—Coal produced in the United States, by States, 1931-41, with production of maximum year and cumulative production from earliest record to end of 1941, in thousands of net tons

		ximum duction					Prod	uction by	years					Total produc tion from
State	Year	Quan- tity	1931	1932	1933	1934	1935	1936	1937	1938	1939	1940	1941	earliest record to end of 1941
Alabama Arkansas Colorado Georgia Illinois Indiana Lowa Kansas Kentucky Maryland Michigan Missouri Montana (bituminous coal and lignite) North Carolina North Dakota (lignite) Ohio Oklahoma Pennsylvania (bituminous coal and lignite) Tennessee Texas (bituminous coal and lignite) Utah Virginia Washington West Virginia Wyoming Other States  Total bituminous coal and lignite. Pennsylvania anthracite.	1903 1918 1918 1917 1918 1927 1907 1907 1917 1918 1918 1922 1941 1920 1920 1910 1911 1913 1920 1941 1918 1920 1941 1918	21, 001 2, 670 12, 483 416 89, 291 30, 679 8, 966 7, 562 69, 124 5, 533 2, 036 5, 533 4, 023 4, 023 4, 023 178, 551 178,	11, 999 1, 154 6, 604 22 44, 303 14, 295 3, 359 3, 621 2, 378 1, 553 1, 513 2 1, 519 20, 411 1, 908 97, 659 4, 721 7, 721	7, 857 1, 033 5, 599 27 33, 475 13, 324 3, 862 1, 953 35, 300 1, 429 4, 046 4, 046 4, 046 12, 125 1, 263 1, 263 1, 274 1, 275 74, 776 3, 538 6, 609 4, 175 3, 609 4, 175 3, 609 4, 175 3, 609 4, 175 3, 609 4, 175 3, 609 4, 175 3, 609 4, 175 4, 855	8, 760 883 5, 230 41 37, 413 13, 761 3, 195 2, 218 36, 100 1, 531 2, 152 1, 226 1, 226 1, 238 79, 296 3, 775 8, 179 1, 139 4, 344 4, 113 333, 631 49, 541	9, 142 857 5, 211 3, 367 2, 198 38, 525 1, 627 627 627 3, 352 2, 566 1, 259 1, 259 1, 208 1, 208 4, 136 9, 377 1, 383 98, 134 4, 136 7, 138 138 139 139 149 159 159 159 169 169 179 179 179 179 179 179 179 179 179 17	8, 505 1, 133 5, 911 (4) 44, 525 15, 650 2, 686 40, 761 1, 678 640 2, 759 1, 389 (1) 1, 956 4, 138 1, 229 91, 405 4, 138 2, 947 9, 667 1, 559 99, 179 5, 178 180	12, 229 1, 623 6, 812 (1) 50, 927 17, 822 3, 961 2, 944 47, 522 1, 704 6, 985 2, 988 1, 597 (1) 2, 215 24, 110 1, 540 109, 887 11, 662 1, 812 117, 926 5, 781 1439, 088 54, 580	12, 440 1, 511 7, 187 (1) 51, 602 17, 765 3, 637 2, 893 47, 986 1, 715 2, 965 1, 715 2, 178 1, 600 111, 002 5, 213 9, 100 3, 810 13, 795 2, 002 118, 646 5, 918 203 445, 531 551, 856	11, 062 1, 197 5, 663 (1) 41, 912 14, 793 3, 103 2, 654 38, 545 1, 281 4, 281 1, 281 1, 281 1, 281 1, 281 1, 281 1, 281 1, 285 1, 281 1, 245 77, 705 4, 472 2, 947 12, 283 1, 567 93, 288 5, 204 48, 545 46, 099	12, 047 1, 152 5, 923 (1) 46, 783 16, 948 2, 675 42, 557 3, 273 2, 804 1, 230 2, 072 20, 289 1, 188 92, 584 5, 185 826 3, 285 13, 531 1, 690 108, 362 5, 325 394, 855 51, 487	15, 324 1, 454 6, 589 (1) 50, 610 18, 869 3, 231 3, 579 49, 141 1, 503 410 3, 097 2, 867 1, 111 22, 218 22, 772 1, 646 116, 603 6, 621 1, 620 1, 620 1, 620 1, 620 1, 620 1, 620 1, 630 1, 630	15, 464 1, 574 6, 949 (1) 54, 703 22, 484 2, 939 4, 008 53, 710 1, 701 3, 254 1, 251 130, 240 7, 045 3, 353 4, 077 18, 441 1, 841 1, 1841 1, 1	681, 863 77, 721 416, 383 (1) 2, 599, 899 794, 145 320, 960 241, 980 1, 393, 922 245, 875 45, 588 225, 237 126, 725 109, 601 (1) 46, 472 1, 426, 518 134, 880 6, 305, 318 272, 907 60, 042 145, 489 408, 677 131, 859 3, 718, 669 298, 687 62, 593
Grand total			441,735	359, 565	383, 172	416, 536	424, 532	493, 668	497, 387	394, 644	446, 342	512, 257	570, 517	24, 733, 807

<sup>1</sup> Included under "Other States."

## SUMMARY BY STATES

Table 14.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States, by States, in 1941

[Exclusive of mines producing less than 1,000 tons]

		Disposition o	f coal produ	ced (net tons)	)		Avera	ge numb	er of em	oloyees	F		
State	Loaded for shipment by rail or water <sup>1</sup>	Shipped by truck or wagon (ex- cluding coal used by mine employees)	Used by mine employees, taken by locomotive tenders at tipple, or other uses at mine?	Used at mines for power and heat and made into beehive coke at mines 3	Total quantity	Average value per ton 4	Under- ground	In strip pits	All others	Total	Average number of days mines were active	Number of man- days worked	Average tons per man per day
Alabama Alaska Arizona, Georgia, Idaho, and Ore-	14, 276, 483 235, 230	964, 368	118, 576	<sup>8</sup> 105, 096 3, 730	15, 464, 523 238, 960	\$2.71 3.95	21, 572 110	141	8, 222 43	24, 935 153	216 311	5, 384, 901 47, 617	2. 87 5. 02
gon	1, 797, 266	19, 468 62, 615 1, 640, 814 7, 314, 004 2, 258, 093 1, 593, 009 343, 747 2, 052, 833 252, 095 173, 168 1, 304, 795	1, 071 4, 180 112, 190 370, 449 380, 731 39, 240 9, 799 620, 169 13, 884 6, 765 18, 365	680 8, 328 326, 701 771, 912 127, 008 16, 204 10, 098 3154, 389 7, 386 11, 197 24, 862	54, 817 1, 574, 172 6, 948, 532 54, 703, 284 22, 483, 929 2, 938, 626 4, 007, 572 53, 710, 346 1, 700, 574 310, 775 3, 145, 288	2.74 3.74 2.83 1.81 1.70 2.74 1.98 2.17 2.40 4.22 2.23	136 3, 267 6, 345 25, 396 5, 186 4, 544 1, 514 48, 780 1, 957 672 2, 856	120 16 1,751 1,885 331 525 159 8	52 601 1,389 6,920 3,194 718 723 7,857 266 85 679	188 3, 988 7, 750 34, 067 10, 265 5, 593 2, 762 26, 796 2, 231 757 4, 188	222 134 213 186 200 158 201 215 216 162 169	41, 659 534, 791 1, 647, 015 6, 343, 392 2, 050, 613 882, 343 555, 831 12, 213, 755 481, 198 122, 619 707, 194	1. 32 2. 94 4. 22 8. 62 10. 96 3. 33 7. 21 4. 40 3. 53 2. 53 4. 45
Bituminous coal Lignite	3, 034, 147 4, 483	147, 578 54, 042	9,000 228	4, 206 40	3, 194, 931 58, 793	1. 48 1. 79	886 68	47 8	350 22	1, 283 98	197 174	252, 817 17, 083	12. 64 3. 44
Total Montana  New Mexico North Dakota (lignite) Ohio Okiahoma Pennsylvania South Dakota (lignite) Tennessee	1, 709, 100 22, 329, 298 1, 572, 187 109, 081, 289 37, 338	201, 620 133, 190 411, 880 6, 833, 165 187, 371 10, 562, 884 33, 364 525, 255	9, 228 11, 180 163, 515 83, 401 3, 029 4, 077, 713 5 123 69, 327	4, 246 39, 658 24, 393 72, 979 8, 521 3 6, 517, 797 (5) 3 38, 860	3, 253, 724 1, 251, 120 2, 308, 888 29, 318, 88, 1, 771, 108 130, 239, 683 70, 825 7, 045, 271	1. 48 3. 03 1. 27 1. 99 2. 65 2. 28 1. 52 2. 34	954 1, 427 562 16, 734 1, 540 105, 899 15 7, 926	55 444 1, 685 183 2, 514 44 3	372 396 269 3, 741 415 15, 075 10 1, 243	1, 381 1, 823 1, 275 22, 160 2, 138 123, 488 69 9, 172	195 219 177 223 171 224 174 218	269, 900 399, 462 225, 657 4, 936, 786 365, 841 27, 605, 388 12, 001 1, 997, 557	12.06 3.13 10.23 5.94 4.84 4.72 5.90 3.53

See footnotes at end of table.

Table 14.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States, by States, in 1941—Continued

	Disposition of coal produced (net tons)						Average number of employees						
State	Loaded for shipment by rail or water	Shipped by truck or wagon (ex- cluding coal used by mine employees)	Used by mine employees, taken by locomotive tenders at tipple, or other uses at mine	Used at mines for power and heat and made into beehive coke at mines	Total quantity	Average value per ton	Under- ground	In strip pits	All others	Total	Average number of days mines were active	Number of man- days worked	Average tons per man per day
Texas: Bituminous coal Lignite	10, 074 329, 947	5, 282 5 7, 379	126	(5)	15, 482 337, 326	\$3.41 .84	57 154	30	11 18	68 202	94 180	6, 405 36, 301	2. 42 9. 29
Total Texas	340, 021 3, 543, 114 17, 412, 546 1, 339, 501 135, 098, 222 6, 315, 262	\$ 12,661 478,271 376,955 400,717 1,717,762 201,534	126 23, 115 99, 276 85, 964 2, 681, 535 36, 354	(5) 3 32, 279 3 552, 169 15, 092 3 752, 729 93, 180	352, 808 4, 076, 779 18, 440, 946 1, 841, 274 140, 250, 248 6, 646, 330	. 95 2. 33 2. 33 3. 52 2. 23 2. 09	211 1, 926 16, 407 1, 712 95, 710 3, 407	30 4 6 248 56	29 719 2, 257 442 17, 791 847	270 2, 645 18, 668 2, 160 113, 749 4, 310	158 207 226 223 228 203	42, 706 546, 872 4, 223, 273 482, 129 25, 907, 185 874, 568	8. 26 7. 45 4. 37 3. 82 5. 41 7. 60
Total United States	455, 424, 808	40, 055, 638	9, 039, 305	3 9, 629, 494	514, 149, 245	2. 19	376, 765	10, 861	69, 355	456, 981	216	98, 902, 253	5. 20

<sup>1</sup> Includes coal loaded at mine directly into railroad cars or river barges, hauled by truck to railroad siding for shipment by rail, and hauled by truck to waterway for shipment by water.

water.

Includes coal transported from mines to points of use by conveyor, chute, or aerial tramway.

Includes coal made into beehive coke at mines in the following States: Alabama, 4,830 tons; Colorado, 124,198 tons; Kentucky, 3,424 tons; Pennsylvania, 6,037,747 tons; Tennessee, 11,920 tons; Utah, 20,106 tons; Virginia, 525,067 tons; and West Virginia, 413,252 tons; a grand total of 7,140,544 tons.

Value received or charged for coal f. o. b. the mine, including selling cost. (Includes a value for coal not sold but used by producer, such as mine fuel and coal coked [not coke] as estimated by the producer at average prices that might have been received if such coal had been sold commercially.)

Since it is necessary to conceal certain items in the lignite break-down of disposition of coal, the figures are included here in the column where the greater part of the concealed

tonnage would appear.

## PRODUCTION BY WEEKS AND MONTHS

Table 15.—Final bituminous-coal and lignite production in the United States, with estimates by weeks, in 1941

		<del></del>	T	11	<del></del>	1	
	Produc-	Num-	A verage produc-		Produc-	Num-	A verage produc-
Wools and d	tion	ber of	tion per	ll	tion	ber of	tion per
Week ended-	(net	work-	working	Week ended-	(net	work-	working
	tons)	ing	day (net		tons)	ing	day (net
		days	tons)		1	· days	tons)
					<u> </u>		
Jan. 4	1 5 160 000	13	9 1 700 000	T1 10	10.011.000		
Jan. 11	10, 371, 000	6	2 1,799,000 1,729,000	July 19 July 26	10, 814, 000	6	1, 802, 000
Jan. 18	9, 880, 000	6	1, 647, 000	Aug. 2	10, 937, 000	6	1, 823, 000
Jan. 25	10, 165, 000	6	1, 694, 000	Aug. 9		6	1, 789, 000
Feb. 1	10, 329, 000	6	1,722,000	Aug. 9	10, 783, 000	6	1, 797, 000
Feb. 8.	10, 318, 000	6	1, 720, 000	Aug. 16 Aug. 23	11,062,000	6	1,844,000
Feb. 15	10, 642, 000	6	1, 774, 000	Aug. 30	11, 307, 000	6	1,844,000
Feb. 22	10, 641, 000	6	1, 774, 000	Sept. 6.	10, 050, 000	5	1, 885, 000 2, 010, 000
Feb. 22 Mar. 1	11, 096, 000	6	1, 849, 000	Sept. 13	11 526 000	6	1, 923, 000
Mar. 8	10, 947, 000	6	1, 825, 000	Sept. 20	10, 459, 000	6	1, 743, 000
Mar. 15	11, 288, 000	6	1, 881, 000	Sept. 27	11, 417, 000	6	1, 903, 000
Mar. 22	11, 493, 000	6	1, 916, 000	Oct. 4	11, 627, 000	6	1, 938, 000
Mar. 29		6	1, 989, 000	Oct. 11	11, 606, 000	6	1, 934, 000
Apr. 5	3, 380, 000	5	676,000	Oct. 18	11, 463, 000	6	1, 911, 000
Apr. 12	1,089,000	6	182,000	Oct. 25	11, 256, 000	6	1, 876, 000
Apr. 19	1, 305, 000	6	218,000	Nov. 1	10, 963, 000	6	1, 827, 000
Apr. 26	1, 612, 000	6	269,000	Nov. 8	11, 398, 000	6	1, 900, 000
May 3	5, 117, 000	6	853,000	Nov. 15	11, 666, 000	5.6	2, 083, 000
May 10	9, 368, 000	6	1, 561, 000	Nov. 22	9,006,000	5. 2	1, 732, 000
May 17	10, 089, 000	6	1, 682, 000	Nov. 29	11, 695, 000	5.8	2,016,000
May 24	10, 475, 000	• 6	1, 746, 000	Dec 6	11 415 000	6	1, 903, 000
May 31	9, 627, 000	5.4	1, 783, 000	Dec. 13	11, 457, 000	6	1, 910, 000
June 7		6	1, 599, 000	Dec. 13. Dec. 20.	11, 224, 000	6	1, 871, 000
June 14		6	1, 698, 000	Dec. 27	8, 469, 000	5	1,694,000
June 21	10, 364, 000	6	1, 727, 000	Jan. 3, 1942	1 6, 378, 000	13	<sup>2</sup> 2,021, 000
June 28	11, 322, 000	6	1, 887, 000				
July 5		3.4	2,019,000		514, 149, 000	303.4	1, 695, 000
July 12	9, 707, 000	5	1,941,000				
	I had a second						

I Figures represent output and number of working days in that part of the week included in the calendar year shown. Total production for the week of January 4, 1941, was 8,994,000 net tons and for January 3, 1942, was 10,104,000 net tons.

3 Average daily production for the entire week and not for the working days in the calendar year shown.

## Table 16.—Final coal production in the United States, by States, with estimates by months, in thousands of net tons, in 1941

[The toals for the year are based upon final complete returns to the Bituminous Coal Division from all operators known to have produced more than 1,000 tons a year. The apportionment of the known yearly total among the 12 months is based upon the best information available—in some States upon direct tonnage reports by operators to the State mine department, in most cases upon current records of railway carloadings and waterway shipments]

	-	l				l <u>.</u>			Septem-	October	Novem-	Decem-	Total
State	January	February	March	April	Мау	June	July	August	ber	October	ber	ber	1 Otal
Alabama Alaska Arkansas Colorado Illinois Indiana Iowa Kansas	1, 444	1, 409	1, 591	191	1. 083	1, 488	1, 404	1, 463	1, 286	1, 244	1, 315	1, 546	15, 464
	21	14	17	19	19	15	22	22	20	23	22	25	239
	205	147	132	19	25	31	85	178	207	210	175	160	1, 574
	768	624	689	306	368	375	446	491	676	702	719	785	6, 949
	5, 493	5, 125	5, 862	968	3, 905	3, 764	4, 538	4, 750	4, 677	5, 063	4, 980	5, 578	54, 703
	2, 153	1, 924	2, 468	194	1, 766	1, 627	1, 666	1, 888	2, 009	2, 259	2, 218	2, 312	22, 484
	343	291	351	130	167	167	167	176	231	277	299	340	2, 939
	416	381	441	249	202	243	275	327	342	353	365	414	4, 008
Kentucky:	3, 577	3, 416	3, 901	162	3, 731	3, 994	3, 922	3, 993	4, 181	4, 474	3, 404	3, 375	42, 130
Eastern	952	960	1, 073	1, 398	866	711	829	886	872	942	1, 004	1, 087	11, 580
Total Kentucky	4, 529	4, 376	4, 974	1, 560	4, 597	4, 705	4, 751	4, 879	5, 053	5, 416	4, 408	4, 462	53, 710
Maryland	153	149	167	14	131	151	146	152	163	162	142	171	1, 701
Michigan	44	39	38	17	6	2	7	28	30	34	32	34	311
Missouri	327	298	347	195	158	191	215	256	269	276	287	326	3, 145
Montana: Bituminous coal Lignite	299 6	256 5	224 5	181 3	184	184	220 3	238 3	289 5	372 8	369 9	379 6	3, 195 59
Total Montana.  New Mexico. North Dakota (lignite). Ohio. Oklahoma. Pennsylvania (bituminous). South Dakota (lignite). Tennessee.	305 113 289 2, 230 231 11, 607 11 595	261 106 237 2, 298 166 10, 962 9 596	229 122 197 2, 676 147 12, 380 6	184 85 87 269 21 242 3 107	187 76 77 2,431 29 11,930 1 591	187 99 88 2,533 34 11,711 1 632	223 95 83 2,592 96 11,500 1 614	241 90 100 2, 739 201 12, 135 1 627	294 103 177 2, 893 233 11, 832 5 651	380 112 306 3, 068 238 12, 949 12 715	378 115 382 2, 805 196 10, 412 12 614	385 135 286 2,785 179 12,580 9 635	3, 254 1, 251 2, 309 29, 319 1, 771 130, 240 71 7, 045
Texas: Bituminous coalLignite	2	2	1	1	1	1	1	1	1	1	2	2	16
	30	27	31	28	26	29	28	29	25	34	29	21	337
Total TexasUtahVirginiaVirginia	32	29	32	29	27	30	29	30	26	35	31	23	353
	431	356	351	61	237	209	242	388	457	472	406	467	4, 077
	1,461	1,385	1,619	234	1, 714	<b>1,</b> 691	<b>1,</b> 696	1,733	1,770	1, 906	1,637	1, 595	18, 441

BITU
BITUMINOUS
SCOAL
LAND
LIGNITE

Washington	11, 129 587 6	150 10, 779 490 5	12, 682 571 4	134 349 440 3	13, 365 382 5	124 12, 976 377 4	12, 773 477 3	13, 431 538 3	173 13, 434 676 4	186 14, 555 745 5	174 11, 956 663 5	12, 821 700 7	1, 841 140, 250 6, 646 54
Total bituminous coal and lignite Pennsylvania anthracite 2	45, 087 5, 162	42, 606 4, 596	48, 926 4, 765	6, 110 3, 317	43, 603 4, 001	43, 455 5, 072	44, 264 4, 855	47, 013 5, 441	47, 691 5, 334	51, 703 5, 580	44, 748 3, 974	48, 943 4, 271	514, 149 56, 368
Grand total	50, 249	47, 202	53, 691	9, 427	47, 604	48, 527	49, 119	52, 454	53, 025	57, 283	48, 722	53, 214	570, 517

<sup>1</sup> Includes Arizona, Georgia, Idaho, and Oregon.

<sup>1</sup> Pennsylvania anthracite figures from Bureau of Mines. Includes Sullivan County, washery and dredge coal, local sales, colliery fuel, and coal shipped by truck from authorized operations; also includes some "bootleg" coal purchased by legitimate operators and prepared at their breakers.

### NUMBER AND SIZE OF MINES

Table 17.—Number and production of bituminous-coal and lignite mines in the United States, classified by size of output in each State, in 1941 [Exclusive of mines producing less than 1,000 tons]

		Class 1A	, more than	500,000 tons	3		Class 1	3, 200,000 to	500,000 ton	3		Class 2	, 100,000 to 2	00,000 tons	
State	Mi	ines	]	Production		Mi	ines	P	roduction		Mi	nes	P	roduction	
	Num- ber	Per- cent	Total (net tons)	Average per mine (net tons)	Per- cent	Num- ber	Per- cent	Total (net tons)	Average per mine (net tons)	Per- cent	Num- ber	Per- cent	Total (net tons)	Average per mine (net tons)	Per- cent
Alabama Alaska Arizona, Georgia, Idaho, and	l	2, 3	4, 772, 359	681, 766	30. 9	14	4.5	4, 941, 533	352, 967	32.0	22 (¹)	7. 1 (¹)	3, 301, 638	150, 074 (¹)	21, 3
Oregon Arkansas Colorado		.5	657, 043	657, 043	9. 5	5	2.4	1, 229, 953	245, 991	17. 7	1 15	1. 2 7. 2	113, 606 2, 143, 199	113, 606 142, 880	7. 2 30. 8
Indiana	13	9. 1 4. 5	38, 100, 812 10, 650, 663 735, 514	846, 685 819, 282 735, 514	69. 7 47. 4	24 23 1	4.8 7.9 .4	8, 497, 011 7, 239, 806 214, 241	354, 042 314, 774 214, 241	15. 5 32. 2 7. 3	17 9 4	3. 4 3. 1 1. 5	2, 667, 784 1, 218, 440 490, 174	156, 928 135, 382 122, 544	4. 8 5. 4 16. 7
Kansas Kentucky Maryland Michigan				864, 802	18. 4 27. 4	7 71 1	7. 5 9. 9 1. 1	2, 243, 317 22, 121, 434 236, 417	320, 474 311, 569 236, 417	56. 0 41. 2 13. 9	3 63 2	3. 2 8. 8 2. 2	390, 036 9, 100, 416 340, 945	130, 012 144, 451 170, 473	9. 7 16. 9 <b>2</b> 0. 0
Missouri Montana (bituminous coal) Montana, North Dakota, South Dakota, and Texas (lignite) New Mexico Ohio	1	2. 0	1, 395, 943	1, 395, 943	43. 7	3 3	1. 5 5. 9	1, 155, 199 1, 303, 249	385, 066 434, 416	36. 7 40. 8	2 2	10. 0 1. 0 3. 9	168, 945 317, 368 281, 335	168, 945 158, 684 140, 668	54. 4 10. 1 8. 8
New Mexico Ohio	17	2. 3	13, 608, 069	800, 475	46, 4		3.1 7.1 1.7	1,710,669 818,583 4,364,844	285, 112 272, 861 335, 757	61. 6 65. 4 14. 9	1 29	3.9	177, 624 4, 405, 675	177, 624 151, 920	6. 4 15. 0
Oklahoma Pennsylvania Tennessee Texas (hituminous coel)	80	5. 0	71, 711, 679	896, 396	55. 1	1 77 12	1.0 4.8 8.2	390, 491 24, 029, 757 3, 555, 987	390, 491 312, 075 296, 332	22. 1 18. 4 50. 5	3 105 12	3. 0 6. 5 8. 2	387, 706 15, 206, 470 1, 738, 807	129, 235 144, 824 144, 901	21. 9 11. 7 24. 7
Utah	3	5. 7 5. 2	1, 827, 351 7, 254, 283	609, 117 906, 785	44. 8 39. 3	2 24 2	3. 8 15. 5	746, 016 7, 904, 846	373, 008 329, 369	18.3 42.9	6 13	11. 3 8. 4	881, 009 1, 932, 663	146, 835 148, 666	21.6 10.5
Washington West Virginia Wyoming	79 4	9. 5 6. 0	64, 651, 065 2, 622, 368	818, 368 655, 592	46. 1 39. 5	155 7	4. 9 18. 7 10. 4	614, 614 48, 580, 086 2, 548, 928	307, 307 313, 420 364, 133	33. 4 34. 6 38. 3	116 6	12. 2 13. 9 9. 0	736, 389 17, 525, 852 993, 849	147, 278 151, 085 165, 642	40. 0 12. 5 15. 0
Total United States	276	4.1	232, 688, 787	843, 075	45. 3	454	6.6	144, 446, 981	318, 165	28.1	437	6. 4	64, 519, 930	147, 643	12. 5

Table 17.—Number and production of bituminous-coal and lignite mines in the United States, classified by size of output in each State, in 1941—Continued

[Exclusive of mines producing less than 1,000 tons]

		Class 3,	50,000 to 100	0,000 tons	3		Class 4	, 10,000 to 50	),000 tons	3	c	lass 5,	less than 10	,000 ton	ıs		Total	
	м	ines	Pro	duction		Mi	nes	Pro	duction		Mi	nes	Proc	luction			Production (	(net tons)
State	Num- ber	Per- cent	Total (net tons)	Average per mine (net tons)	Per- cent	Num- ber	Per- cent	Total (net tons)	Average per mine (net tons)	Per- cent	Num- ber	Per- cent	Total (net tons)	A ver- age per mine (net tons)	Per- cent	Mines	Total	Average per mine
Alabama	15 1 3	4.8 1100.0	1, 134, 570 1 238, 960	75, 638 179, 653	7.3 1100.0	32 (¹)	10. 3 (¹)	676, 049 (¹)	21, 127 (¹)	4.4 (1)	220	71, 0	638, 374	2, 902	4.1	310 3	15, 464, 523 238, 960	49, 886 79, 653
Arizona, Georgia, Idaho, and Oregon	8 20 24 19 6 1 55 6	9.5 9.6 4.9 6.5 2.2 1.1 7.7 6.8	591, 413 1, 414, 643 1, 575, 243 1, 380, 243 462, 693 58, 421 4, 216, 876 423, 318 167, 596 53, 497	73, 927 70, 734 65, 635 72, 644 77, 116 58, 421 76, 670 70, 553 83, 798 53, 497	37.6 20.4 2.9 6.1 15.7 1.4 7.8 24.9 5.3 1.7	1 32 45 125 64 56 20 97 20 6 42 2	11. 1 38. 1 21. 6 25. 3 21. 9 20. 9 21. 5 13. 5 22. 5 60. 0 20. 9 3. 9	35, 674 724, 622 1, 078, 323 2, 833, 540 1, 401, 142 1, 032, 891 345, 568 2, 294, 190 528, 287 127, 819 1, 008, 541 39, 208	35, 674 22, 644 23, 963 22, 668 21, 893 18, 444 17, 278 23, 651 26, 414 21, 303 24, 013 19, 604	65. 1 46. 0 15. 5 5. 2 8. 6 4. 3 31. 1 41. 1 32. 1 1. 2	8 43 122 260 164 201 61 414 60 3 152 42	88. 9 51. 2 58. 7 52. 5 56. 1 75. 0 65. 6 57. 7 67. 4 30. 0 75. 6 82. 3	19, 143 144, 531 425, 331 1, 028, 892 593, 635 738, 627 234, 716 1, 275, 792 171, 607 14, 011 496, 584 121, 699	2, 393 3, 361 3, 486 3, 957 3, 620 3, 675 3, 848 3, 082 2, 860 4, 670 3, 267 2, 898	34. 9 9. 2 6. 1 1. 9 2. 7 25. 1 5. 9 2. 4 10. 1 4. 5 15. 8 3. 8	9 84 208 495 292 268 93 717 89 10 201 51	54, 817 1, 574, 172 6, 948, 532 54, 703, 284 22, 483, 929 2, 938, 626 4, 007, 572 53, 710, 346 1, 700, 574 310, 775 3, 145, 288 3, 194, 931	6, 091 18, 740 33, 406 110, 512 77, 000 10, 965 43, 092 74, 910 19, 108 31, 078 15, 648 62, 646
South Dakota, and Texas (lignite). New Mexico Ohio. Oklahoma. Pennsylvania. Tennessee. Texas (bituminous coal). Utah. Virginia. Washington. West Virginia. Wyoming.	25 4 104 13 3	2.6 4.8 3.3 3.9 6.4 8.9 5.7 6.4 2.4 8.9 1.5	358, 414 180, 811 1, 828, 708 239, 967 7, 513, 875 913, 041 220, 755 740, 050 61, 397 5, 605, 991 67, 187	71, 683 90, 406 73, 148 59, 992 72, 249 70, 234 73, 585 74, 005 61, 397 75, 757 67, 187	12.9 14.5 6.2 13.5 5.8 13.0 5.4 4.0 3.3 4.0 1.0	12 9 143 24 372 25 1 12 15 15 15 121	6. 1 21. 4 19. 2 23. 5 23. 1 17. 1 33. 3 22. 6 9. 7 36. 6 14. 6 20. 9	219, 442 176, 169 3, 424, 332 503, 323 8, 632, 384 580, 512 11, 382 287, 553 359, 488 362, 140 2, 954, 696 309, 075	18, 287 19, 574 23, 946 20, 972 23, 205 23, 220 11, 382 23, 963 23, 966 24, 143 24, 419 22, 077	7.9 14.1 11.7 28.4 6.6 8.2 73.5 7.1 1.9 19.7 2.1 4.6	171 28 519 70 873 84 2 27 85 18 286 35	87. 7 66. 7 69. 6 68. 6 54. 2 57. 6 66. 7 50. 9 54. 8 43. 9 34. 4 52. 2	309, 683 75, 557 1, 687, 215 249, 621 3, 145, 518 256, 924 4, 100 114, 095 249, 616 66, 734 932, 558 104, 923	1, 811 2, 698 3, 251 3, 566 3, 603 3, 059 2, 050 4, 226 2, 937 3, 707 3, 261 2, 998	11. 2 6. 0 5. 8 14. 1 2. 4 3. 6 26. 5 2. 8 1. 4 3. 6 7	195 42 746 102 1,611 146 3 53 155 41 831 67	2, 775, 832 1, 251, 120 29, 318, 843 1, 771, 108 130, 239, 683 7, 045, 271 15, 482 4, 076, 779 18, 440, 946 1, 841, 274 140, 250, 248 6, 646, 330	14, 235 29, 789 39, 301 17, 364 80, 844 48, 255 5, 161 76, 920 118, 974 44, 909 168, 773 99, 199
Total United States	402	5.9	29, 447, 711	73, 253	5.7	1, 305	19.1	29, 946, 350	22, 947	5.8	3, 948	57.9	13, 099, 486	3, 318	2.6	6, 822	514, 149, 245	75, 366

<sup>1</sup> In Alaska, 1 mine that should be included in class 2 and 1 mine that should be included in class 4 are included in class 3 to avoid disclosure of individual operations.

#### AVERAGE VALUE

Before the Bituminous Coal Act of 1937 was passed, the most valuable single index of the trend of prices at the mines was the "average value per ton, f. o. b. mines," as given in the familiar annual coal reports of the Bureau of Mines, United States Department of the Interior. This series was referred to in Bureau of Mines reports as representing "bituminous coal," and it covered all coal (other than Pennsylvania anthracite) produced in the United States. It represented the bituminous-coal industry as the term ordinarily was used in the trade and included the lignite of the Dakotas, Texas, and Montana, as well as any small tonnages of hard coal produced outside of Pennsylvania.

With the passage of the Coal Act, the Bureau of Mines relinquished the collection of statistics relating to bituminous coal, effective June 30, 1937, though continuing to compile data regarding lignite and Pennsylvania anthracite. Effective the same date, the Coal Commission became responsible for the compilation of data on bituminous coal, though not attempting to collect data regarding lignite, which was specifically exempted by the act. The records of the Commission (now Bituminous Coal Division, United States Department of the Interior) relate to all coal other than Pennsylvania

anthracite, Virginia semianthracite, and lignite.

To permit comparison of the old and new series, therefore, it is necessary to separate the lignites from the bituminous coals, though for the convenience of the student the combined average for the two is continued in a form as nearly comparable as possible to the old

series. (See table 18.)

A more important change in the two series relates to the treatment of selling expenses. The old Bureau of Mines series of "value at the mines" excluded the selling cost. Reporting operators were asked to state the "Amount received at the mines f. o. b. cars less the selling expense." No details were asked regarding the items included in the value, and no systematic effort was made to follow up the exclusion of selling expenses. It was realized at the time that some producers might find it impractical to exclude selling costs and that some part of the selling expenses of the industry might be included in the results. Nevertheless, the reports were checked for consistency from year to year, the questions were retained in the same form without change, and the results are believed to have been comparable from one year to the next. The new series of the Coal Commission represents the total or gross realization on all coal produced and specifically includes the selling cost.

The two sets of data may not be precisely comparable with respect to coal produced but not sold on the commercial market. In the Bureau of Mines series reporting operators were instructed that the "value of coal not sold but used by producer, also mine fuel and coal made into coke should be estimated at average prices that might have been received." The instructions of the Coal Commission regarding such items were in effect similar, though given in greater

detail.

A comparison of the two series is possible for 1936. In that year the average value per ton on the old (Bureau of Mines) basis amounted to \$1.761 per ton for bituminous coal, excluding lignite. The aver-

A STATE OF THE STA

age gross realization, according to data collected by the Coal Commission, was \$1.831 per ton. The difference amounts to \$0.07 per ton—an amount somewhat less than the average selling expenditure computed per ton of all coal produced, as reported to the Coal Commission. The comparison confirms previous indications that the great majority of operators reporting in earlier years had followed instructions and omitted selling expenses in computing the average value but that some of them had included the selling expense. The change in method of reporting should be kept in mind in comparing the two sets of data. As the reports to the Commission were submitted on a detailed accounting return and made under oath they are to be accepted. The returns of earlier years, upon a voluntary basis and not in all instances uniform as to treatment of selling costs, seem to have been thoroughly comparable from one year to the next and afford the best available index to the rise and fall of the mine prices received by operators down to 1936.

Table 18.—Trend of average value in the United States of bituminous coal and lignite per ton, f. o. b. mines, 1929-41

Year	Bituminous coal (subject to regulation under 1937 act) 1	Lignite 3	Total
Average value per ton less selling cost (Bureau of Mines series):  1929	\$1. 782	\$1. 549	\$1. 781
	1. 702	1. 556	1. 701
	1. 542	1. 410	1. 541
	1. 313	1. 313	1. 313
	1. 337	1. 188	1. 336
	1. 751	1. 387	1. 749
	1. 772	1. 120	1. 767
	1. 761	1. 061	1. 756
	1. 831	\$1. 061	1. 826
	1. 946	\$1. 080	1. 939
	1. 995	\$1. 071	1. 947
	1. 850	1. 158	1. 845
	1. 913	\$1. 156	1. 908
	2. 194	\$1. 156	2. 189

<sup>1</sup> Includes all coal produced other than Pennsylvania anthracite and the lignite included in the second column.

4 Producers were asked to exclude selling cost in reporting value, but a number of them included such costs.

### LABOR STATISTICS

Men employed.—An average of 456,981 men was employed at bituminous-coal mines in 1941, a 4.1-percent increase over the total of 439,075 for 1940 (see fig. 8). Statistics on men employed in 1941 represent annual averages of the number of workers on the rolls on the days when the mines were in operation.

The method used here in calculating employment gives an accurate measure of the working force in the coal industry, but it does not consider the time lost by men on the rolls through intermittent operations. To measure the influence of intermittency upon employment the factor of mine activity as indicated by the average number of days of

North Dakota, South Dakota, and the lignite counties of Montana and Texas.
 Figures from the Bureau of Mines. Data on sales realization were not collected from lignite mines by the Bituminous Coal Division. Figures for 1936-38 and 1940 exclude selling cost as before. Figure for 1941 includes selling cost.

plant operation was recorded separately. The average number of men employed when the mines were in operation was then used, in conjunction with the average number of days of operation, as a

measure of the total volume of employment in the industry.

Days operated.—The average number of days of operation at bituminous-coal mines in 1941 was 216. This represents an increase over the average of 202 days for 1940. All statistics on days of mine operation included in this report are weighted averages, in which the operating time of each mine has been weighted by the number of its employees. Several coal-mining States publish series on the number of days worked that are simple averages of the figures for each reporting mine, regardless of size. As these unweighted averages are likely to be unduly depressed by small mines, which generally operate fewer days than the larger ones, they tend to understate the working time of a typical mine employee.

Man-days of labor.—Only a small proportion of the bituminous-coal-mine operations, however, keep an accurate record of man-days or man-hours worked. Consequently, man-days have been computed by multiplying the number of workers employed by the number of operating days. Although these computations were made for each individual mine, the combined total is necessarily only an approxi-

mation.

Until the American coal industry arranges to keep an accurate record of man-days or man-hours of employment all computations of accident rates, daily earnings, and output per man will remain subject to qualification. Meanwhile, the method of multiplying men by days must be accepted as the best available procedure.

Data for 1941 indicate that bituminous-coal-mine employees performed 98,902,253 man-days of labor during the year. Table 14 gives a summary record of men employed, days operated, and output per man per day at bituminous-coal mines, by States, in 1941. De-

tails by counties for 1941 are shown in table 40.

Length of working day.—Table 19 summarizes the replies of mine operators to the question, "Number of hours operated per shift."

The reports of more than 7 hours of work per shift in 1941 consist partly of (1) work for which the operator has included time when the men are entering or leaving the mine, (2) work for which the operator has reported the time of certain employees who work longer than other employees, as in stripping overburden, or (3) operations where work is staggered and two crews of men overlap. There were, however, a number of mines in 1941 where the established day was 8 hours. As shown by the table, most of these were very small. Numerous mines, especially the smaller ones, failed to answer the question.

It was found that 92.6 percent of the men employed were in 7-hour mines and that the weighted average working shift was 7.03 hours.

The established working day does not of itself measure the length of time that men actually work or the time that they are underground, because of the possibility of overtime, because the mine may sometimes shut down before the full day is over, because the miner may go home before the mine stops, and because he spends a considerable time going to and from his place of work underground.

As interpreted in the wage agreements, the 7-hour day means 7 hours of labor at the usual working place, exclusive of any time for

lunch and exclusive of the time spent in going from the entrance of the mine to the working place and back again. As noted, these figures represent the operator's statement of the nominal operating day for the mine. They do not purport to represent the time actually worked by the men. On the one hand, they make no allowance for tonnage or piece workers who leave early; on the other hand, they make no allowance for tonnage men who continue at work after the mine as a whole is shut down, or who go into the mine to work on days when the tipple is idle.

Table 19.—Number of bituminous-coal and lignite mines in the United States having established working shift of certain length and number of men employed therein, in 1941

State	7	hours	8 h	ours	9 h	ours	Allo	thers 1	т	otal
State	Mines	Men	Mines	Men	Mines	Men	Mines	Men	Mines	Men
Alabama Alaska Arizona, Georgia, Idaho,	293	24, 424	12	159 153			5	352	310 3	24, 935 153
and Oregon			. 8	182			1	6	9	188
Arkansas	73	3,882	5	47	1	2	5	57	84	3, 988
ColoradoIllinois	151	7, 214	23	177			34	359	208	7, 750
Indiana	380	30, 534	62	778			53	2, 755	495	34, 067
Indiana Iowa	146 164	6,039	60	473	2	12	84	3,741	292	10, 265
Kansas	35	4, 417 1, 393	85 40	915 443	5	59	14 17	202 919	268 93	5, 593
		= -,000					11	919	93	2, 762
Kentucky: Eastern	360	44 000	110	0 000						
Western	173	44, 238	116	3,033			14	701	490	47, 972
	1/0	7,729	47	684			7	411	227	8,824
Total Kentucky	533	51, 967	163	3,717			21	1, 112	717	56,796
Maryland	78	2,052	11	179					89	2, 231
Michigan	8	682					2	75	10	757
Missouri	73	1,906	103	1,607	5	56	20	619	201	4, 188
Montana:										
Bituminous coal	35	1, 146	16	137		-			-	
Lignite	6	44	8	35			6	19	51 20	1, 283
i								19	20	98
Total Montana	41	1, 190	24	172			6	19	71	1, 381
New Mexico	24	1, 661	16	135			2	27	42	1, 823
North Dakota (lignite)	10	167	96	874	5	32	44	202	155	1, 275
Ohio	546	19,832	158	1,667	3	70	39	591	746	22, 160
Oklahoma	83	1,771	12	168	1	4	6	195	102	2, 138
Pennsylvania South Dakota (lignite)	1,336	117, 312	171	1,636	3	14	101	4, 526	1,611	123, 488
Fennessee	(2) 116	(2)	26	2 46	2	7.	6	16	14	69
i ennessee	110	8, 378	28	522			2	272	146	9, 172
Γexas:										
Bituminous coal	1	. 7	1	36		Î	1	25	3	
Lignite			5	152			i	50	. 6	68 202
. }-										202
Total Texas	1	7	- 6	188			2	75	9	270
	36	2, 517	17	128					53	2,645
Virginia	120	18, 101	31	327			4	240	155	18,668
West Virginia	41 726	2, 160							41	2, 160
Wyoming	726 52	111, 497	76	1, 257	1	4	28	991	831	113, 749
· I:	02	4, 187	10	29	1	6	4	88	67	4, 310
Total United States	5,066	423, 290	1, 226	15, 979	30	273	500	17, 439	6, 822	456, 981

Includes mines where the day was more than 9 or less than 7 hours or was irregular; also includes some mines which failed to answer.
 Mines and men working "7 hours" included under "8 hours" for South Dakota lignite.

Table 20.—Strikes, suspensions, and lock-outs in bituminous-coal and lignite mines in the United States, by States, in 1941

State	Number of men	Number of men	Man-days idle on		number of st on ac- of strike
DUALO	employed	on strike	account of strike	Per man employed	Per man on strike
Alabama Alaska	24, 935 153 188	18, 558 50	718, 801 200	29 1	39 4
Arizona, Georgia, Idaho, and OregonArkansas	3, 988 7, 750 34, 067 10, 265 5, 593 2, 762 56, 796	1, 772 5, 904 22, 757 6, 542 2, 178 61 42, 154 1, 756 415 852	69, 775 98, 366 629, 873 162, 198 83, 862 668 1, 123, 975 55, 066 9, 515 42, 821	17 13 18 16 15 (1) 20 25 13 10	39 17 28 25 39 11 27 31 23 50
Montana: Bituminous coalLignite	1, 283 98				
Total Montana  New Mexico  North Dakota (lignite)	1, 381 1, 823 1, 275	460	7, 959	4	17
North Dakota (lighite) Ohio Oklahoma Pennsylvania South Dakota (lighite)	22, 160 2, 138 123, 488	14, 120 497 101, 966	391, 325 45, 564 2, 737, 304	18 21 22	28 95 27
Tennessee	1	6, 533	186, 232	20	29
Texas: Bituminous coal Lignite	68 202				
Total Texas	2, 645 18, 668 2, 160 113, 749	1, 821 14, 372 190 100, 546 341	38, 759 329, 030 5, 320 2, 474, 995 6, 688	22	2 2 2 2 2 2 2
Total United States	456, 981	343, 845	9, 218, 296	20	2

<sup>1</sup> One-half day or less.

# BITUMINOUS COAL AND LIGNITE LOADED FOR SHIPMENT BY INDIVIDUAL RAILROADS AND WATERWAYS

Table 21.—Bituminous coal and lignite loaded for shipment by railroads and waterways in the United States, as reported by mine operators, in net tons, in 1941 1

		19	41
Route	State	By State	Total for route
RAILROADS			
Alabama Central Alabama Great Southern Alaska. Algers, Winslow & Western Alton Alton & Southern Arkansas Western Artemus-Jellico  Atchison, Topeka & Santa Fe	Illinois	183, 295 193, 246 235, 230 3, 052, 345 777, 160 21, 506 7, 008 5, 934 423, 607 215, 420 581, 149 512, 039 13, 774 749, 137	183, 295 193, 246 235, 230 3, 052, 345 798, 666 7, 008 5, 934 423, 607  2, 071, 519

Table 21.—Bituminous coal and lignite loaded for shipment by railroads and waterways in the United States, as reported by mine operators, in net tons, in 1941—Continued

		194	11
Route	State		Total for
		By State	route
RAILROADS—continued		107 544	
	Illinois	187, 544 553, 076	
	Indiana Maryland	127, 092	33, 134, 49
Baltimore & Ohio	li Ohio	127, 092 3, 300, 967 11, 134, 481	00, 104, 40
	Pennsylvania West Virginia	17, 831, 336	
Ressemer & Lake Erie		4, 070, 058	4, 070, 08 351, 70 622, 34
Bessemer & Lake ErieBevier & Southern	Missouri	351,709	351, 70
	Missouri. West Virginia. Pennsylvania.	11, 134, 481 17, 831, 336 4, 070, 058 351, 709 622, 345 4, 886, 391 1, 070, 993 437, 478 58, 834	4, 886, 39
Campbell's Creek		1,070,993	1, 070, 99
Sunato Creek & Gattley  Sambria & Indiana  Sampbell's Creek  Carbon County	Utah	437, 478 58 834	437, 47 58, 8
Jasevviiie	Illinois   Alabama		1,069,77
Central of Georgia		33, 598	{ 1,000,77
Chesapeake & Ohio		33, 598 8, 211, 952 611, 479	52, 316, 59
	II West virginia	43, 493, 159	
Cheswick & Harmar	Pennsylvania	907, 251 1, 462, 404 1, 624, 072	907, 2
Chicago & Eastern Illinois	l) Indiana	1, 624, 072	3, 086, 47
Chicago & Illinois Midland	I Illinois	5,656,444	5, 656, 44
Chicago & North Western	{do	2, 740, 528 17, 416	2,757,94
Chicago, Attica & Southern	Indiana (Colorado Illinois	17, 416 11, 402	11, 40
Onicugo, 1111100 & 1011111	Colorado	375, 191	]
Chicago, Burlington & Quincy	Innois	7, 803, 196 257, 934 65, 390 717, 903	9, 219, 6
Chicago, Burmigton & Quincy	Iowa Missouri Wyoming	65, 390	
	Wyoming	717, 903 2, 973	2,9
Chicago Great WesternChicago, Indianapolis & Louisville	I Indiana	1, 324, 634	1, 324, 6
Chicago, indianapons & nodes mo		5, 201, 965 423, 184	1
	Iowa Missouri	1 1.608	
Chicago, Milwaukee, St. Paul & Pacific	(Montana (bituminous)	790, 172	6, 491, 5
Onlargo, 111 action, 211	North Dakota (lignite)	66, 731	
	Montana (bituminous) North Dakota (lignite) South Dakota (lignite) Washington	7,880 14,233	)
	I Arkansas		1
City Deal Taland & Deales	Illinois	585, 629 222, 073	1, 033, 3
Chicago, Rock Island & Pacific	lowa Missouri	113, 737	
	I Oklahoma	97, 635	466, 4
Chicago, Springfield & St. Louis	IllinoisdoIndiana	4, 547, 941	6, 875, 9
Cleveland, Cincinnati, Chicago & St. Louis	[Indiana	1 2, 328, 010	0,010,9
Clinchfield	Kentucky	168, 596	3,048,0
C. J J. C. C C	Kentucky   Virginia   Colorado	2, 879, 468 117, 443	117, 4
Colorado & Southern	do	1 639 X53	639, 8 653, 6
Colorado & Southers. Colorado & Southers. Colorado & Southers. Conemangh & Black Lick. Crystal River & San Juan. Cumberland & Pennsylvania.	Pennsylvania	653, 698 46, 805	1 46.8
Crystal River & San Juan	Colorado	. 60	590, 2
Cumberland & Pennsylvania	Maryland	590, 202 22, 938	22.9
Dardanelle & Russellville	Colorado	1 93, 528	22, 9 93, 5
		1, 367, 168	3, 489, 1
Denver & Rio Grande Western	New Mexico Utah	2, 094, 086 838, 797 81, 693 18, 059	
Denver & Salt Lake	Colorado	838. 797	838, 7 81, 6
Des Moines & Central Iowa	lowaOhio	18, 059	18,0
Detroit, Toledo & Ironton  East Broad Top Railroad & Coal Co  Eastern Railway & Lumber Co	Pennsylvania	.] 000,401	558, 2
Eastern Railway & Lumber Co	Washington		, ,
Erie		1, 340, 701	1, 345, 1
	Indiana	5, 853	5,8
Evansville & Ohio Valley Evansville, Suburban & Newburgh		196, 788	196, 7 22, 3
Fort Dodge, Des Moines & Southern	Oklahoma	189, 157	189, 1
Evansville, Suburban & Newburgh Fort Dodge, Des Moines & Southern Fort Smith & Van Buren Fort Smith & Western Fort Smith, Subiaco & Rock Island Galesburg & Great Eastern	doArkansas	11,235	11, 2 29, 1
		29, 182	

Table 21.—Bituminous coal and lignite loaded for shipment by railroads and waterways in the United States, as reported by mine operators, in net tons, in 1941—Continued

		19	941
Route	State	By State	Total for route
RAILEOADS—continued		gradus (f.)	
Grand Trunk	Michigan	20, 236	20, 23
	Montana (bituminous coal)	473, 387	20, 23
Great Northern	North Dakota (lignite)   Washington	394, 190	996, 810
Gulf, Mobile & Ohio	Alabama	129, 233 141, 657	1 000 000
Harriman & Northeastern	Tennessee	819, 039	960, 696
Huntingdon & Broad Top Mountain Railroad & Coal Co.	Pennsylvania	133, 272 225, 321	133, 272 225, 321
Illinois Central	Illinois	240, 785 9, 652, 654	15 005 05.
Timois Ochuai	Indiana	1 137 021	15, 927, 955
Illinois Terminal	Kentucky Illinois	5, 897, 495 281, 946 483, 593	281, 946
Indiana	Indiana	483, 593	483, 593
International-Great Northern 2	Texas (lignite)	z 329. 947	2 329, 947
Interstate	{Kentucky  Virginia	41, 291 2, 529, 842	2, 571, 133
Iowa Southern Utilities Co	Pennsylvania	97, 279 224, 116	97, 279 224, 116
John Pittsburg	Kansas	254, 062	254, 116
Kanawha Central	West Virginia (Arkansas	254, 062 216, 219 974	254, 062 216, 219
Kansas City Southern	Kansas €	747, 783 47, 724 11, 468	796, 481
Kansas, Oklahoma & Gulf	Oklahoma	47, 724 11, 468	J 11, 468
Kansas, Oklahoma & Gulf Kelley's Creek & Northwestern	West Virginia	1, 674, 990	1, 674, 990
Lake Erie, Franklin & Clarion	Kentucky Pennsylvania	782, 926 790, 046	782, 926 790, 046
Laramie, North Park & Western	Colorado	8 340	8, 349 97, 027
Keiticky's Creek & Northwestern Kentucky & Tennessee Lake Erie, Franklin & Clarion Laramie, North Park & Western Ligonier Valley Litchfield & Madison	Pennsylvania Illinois	97, 027 730, 238 2, 628, 664	97, 027 730, 238
	[Alabama	2, 628, 664	1 100, 200
Louisville & Nashville	Illinois	1, 829 29, 169, 578	33, 402, 204
	Kentucky Tennessee	1, 133, 915 468, 218	33, 402, 204
Mary Lee	(Virginia Alabama	468, 218	J 002 449
Michigan Central	Michigan	983, 443 6, 766	983, 443 6, 766
Midland Valley	Arkansas Oklahoma	6, 766 469, 686 135, 882	605, 568
Minneapolis & St. Louis	∫Illinois.	711, 342 1	{
Minneapolis, St. Paul & Sault Ste. Marie	(10W8	126, 132	} 837, 474
Missouri-Illinois	North Dakota (lignite)	126, 132 572, 913 30, 631	572, 913 30, 631
	Kansas	157, 552 34, 273	],
Missouri-Kansas-Texas	Missouri   Oklahoma	210 063 1	401, 888
	(Texas (lignite)	(2)	j
	Illinois	(2) 745, 943 5, 023, 517 1, 129, 746	
Missouri Pacific	{Kansas	1, 129, 746	7, 303, 505
	Missouri Oklahoma	378, 751 25, 548	
Monessen Southwestern	Pennsylvania	40, 291	40, 291
Monongahela	{do West Virginia	40, 291 2, 226, 400 10, 783, 004	} 13, 009, 404
Montana, Wyoming & Southern	Montana (bituminous coal) Pennsylvania	373, 931 5, 391, 635	373, 931 5, 391, 635
Montour Morehead & North Fork	Pennsylvania Kentucky	5, 391, 635 1, 302	5, 391, 635 1, 302
Nashville, Chattanooga & St. Louis	Alabama Tennessee	232	} 912, 356
New York Central (includes coal shipped over Kanawha & Michigan, Kelley's Creek, Toledo & Ohio Central, and Zanesville &	Tennessee Ohio Pennsylvania West Virginia	912, 124 5, 782, 557 5, 095, 929 964, 848	} 11, 843, 334
Western). Nicholas, Fayette & Greenbrier	West Virginia	964, 848 2, 535, 759	2, 535, 759
Norfolk & Western	Kentucky Virginia	4, 772, 265 9, 936, 735	2, 555, 759 48, 952, 550
	[West Virginia	34, 243, 550	,
Northern Alabamal	Alabama	114, 486	114. 486

Table 21.—Bituminous coal and lignite loaded for shipment by railroads and waterways in the United States, as reported by mine operators, in net tons, in 1941—Continued

		19	941
Route	State	By State	Total for route
RAILROADS—continued			
Northern Pacific	Montana (bituminous coal) North Dakota (lignite)	1, 396, 657 717, 087	3, 086, 11
	Washington	972, 375	
Oneida & Western	Tennessee	35, 350	35, 35
racine Coast	Washington	35, 350 199, 064 171, 980	199,06
	Indiana	3, 494, 987	
Pennsylvania (includes Pittsburgh, Cincinnati, Chicago & St. Louis).	Ohio   Pennsylvania	6, 022, 252 37, 866, 786	48, 666, 87
	Pennsylvania West Virginia	1, 110, 873 330, 923	
Peoria Terminal	Illinois Michigan	330, 923 92, 643	330, 92 92, 64
Pere Marquette Pittsburg & Shawmut	Pennsylvania	1 629 460	1, 628, 46
Pittsburg County	Oklahoma	8, 142	8, 14
Pittsburgh & Lake Erie	Pennsylvania	8, 142 3, 590, 629 809, 501	3, 590, 62
Pittsburgh & West Virginia	Ohio Pennsylvania West Virginia	1.000.004	2, 067, 51
Pittsburgh, Chartiers & Youghiogheny	West Virginia   Pennsylvania	189, 951	2, 50
Pittsburgh, Lisbon & Western	fOhio	2, 508 20, 642	} 24,88
	Ohio Pennsylvania	4, 239	,
Pittsburg, Shawmut & NorthernPreston	West Virginia	674, 911 190, 159	674, 91 190, 1
Rio Grande Southern	I Colorado		6, 76
Rockdale, Sandow & SouthernSt. Louis & Hannibal	Texas (lignite)	(2)	(²) 2, 36
St. Louis & O'Fallon	Illinois	2, 360 368, 123	368, 1
	(Alabama	1.366.446	)
St. Louis-San Francisco	Arkansas Kansas	210, 159 842, 746 380, 371	3, 635, 0
Je. Boulb San Flanoisco	Missouri	380, 371	(,, 000, 0
St. Louis Southwestern of Texas	(Oklahoma	835, 333	) m
Seaboard Air Line	Texas (lignite) Alabama	101, 261 2, 496, 801	(2) 101, 20
	l do	2, 496, 801	)
	Illinois Indiana	3, 244 1, 304, 345	
Southern	Kentucky	1, 194, 107	9, 369, 9
	Tennessee Virginia	2, 953, 063 1, 418, 391	
Southern Pacific	New Mexico	290, 013	290, 0
Southern Pacific Springfield Terminal	Illinois	503 177	503 1
Susquehanna & New York	Pennsylvania Tennessee	2,000 828,726 415,379	2, 0 828, 7: 415, 3
Pennessee Pennessee Central Pennessee Coal, Iron & Railroad Co	ido	415, 379	415, 3
Tennessee Coal, Iron & Railroad Co	Alabama	2, 957, 071 10, 074	2, 957, 0 10, 0
Texas Short Line	Texas (bituminous coal) Texas (lignite)	(2)	(2)
Thomas & Sayreton	Alabama	(2) 795, 564	(2) 795, 50
Toledo, Peoria & Western	Illinois Pennsylvania	120, 186 138, 885	120, 18 138, 8
O MOH.	(Colorado	642, 551	100,0
Union Pacific	Utah	642, 551 26, 244	6, 279, 5
	Washington	30, 839 5, 579, 943	
Unity	Pennsylvania	778 645	776, 6 935, 3
Utah	UtahVirginia	985, 306 179, 892 12, 875, 857 1, 551, 207	•
Virginian	West Virginia	12, 875, 857	13, 055, 7
Wabash	Illinois	1, 551, 207	
w anasi	Iowa Missouri		2,041,5
Western Allegheny	Pennsylvania	216, 092	216,0
Western Maryland	Maryland Pennsylvania	433, 787 216, 092 709, 915 513, 079	5, 338, 5
*	Pennsylvania West Virginia	4, 115, 576	0,000,0
West Virginia Northern	do	211 413	311, 4
Wheeling & Lake Erie	Ohio West Virginia	4, 770, 461 85 665	4, 770, 4 85, 6
Woodward Iron Co	Alabama.	4, 770, 461 85, 665 841, 879	841, 8
· ·			
Total railroad shipments		425, 184, 319	425, 184, 3

Table 21.—Bituminous coal and lignite loaded for shipment by railroads and waterways in the United States, as reported by mine operators, in net tons, in 1941—Continued

		19	41
Route	State	By State	Total for route
WATERWAYS			1000
Allegheny River Black Warrior River Illinois River Kanawha River	Alabama Illinois West Virginia	195, 480 489, 375 2, 127, 532	1, 048, 724 195, 480 489, 375 2, 127, 532
Monongahela River	{Pennsylvania  West Virginia  Ohio	24, 490, 010 242, 041 934, 094	24, 732, 051 934, 094
Ohio River	Kentucky	219, 836 54, 886 1, 869 412, 952	689, 543
Youghiogheny River  Total waterway shipments		23, 690 30, 240, 489	30, 240, 489
Total loaded at mines for shipment by railroads and waterways.		455, 424, 808	455, 424, 808
Shipped by truck or wagon.  Taken by locomotive tenders at tipple.  Shipped by conveyor belt or tram to point of		6, 067, 697	40, 055, 638 1, 099, 582 6, 067, 697
consumption.  Coal used by employees Used at mine for power and heat Made into beehive coke at mine		1, 872, 026 2, 488, 950 7, 140, 544	1, 872, 026 2, 488, 950 7, 140, 544
Total production		514, 149, 245	514, 149, 245

Includes coal loaded at mine directly into railroad cars or river barges, hauled by truck to railroad siding for shipment by rail, and hauled by truck to waterway for shipment by water. In general, the figures show the quantity of bituminous coal and lignite originated for each railroad and waterway, as reported by the mine operators. It must be noted that in 1 year an operator may report coal loaded on the subsidiary railroad and in another year the same operator may report coal loaded on the parent railroad system.

Texas lignite mines shipping over the Missouri-Kansas-Texas, Rockdale, Sandow & Southern, St. Louis Southwestern of Texas, and the Texas Short Line have been included with the International-Great Northern.

# METHODS OF RECOVERY Table 22.—Bituminous coal and lignite mined by different methods in the United States, by States, in 1941

		17	From un	derground	workings			From stri	ip pits	
State	Mined by	hand	Shot off th	ne solid	Cut by ma	achines	Total		n	Grand total
Diate	Net tons	Percent of total under- ground	Net tons	Percent of total under- ground	Net tons	Percent of total under- ground	under- ground (net tons)	Net tons	Percent of grand total	production (net tons)
Alabama	449, 362 69, 665 2, 180	2. 9 29. 2 4. 0	3, 206, 397 169, 295 52, 637	21. 1 70. 8 96. 0	11, 570, 317	76.0	15, 226, 076 238, 960 54, 817	238, 447	1.5	15, 464, 523 238, 960 54, 817
Arkansas Colorado Illinois Indiana.	3, 566 1, 615, 196 747, 639 41, 011	23.3 1.8	130, 015 420, 597 1, 989, 054 508, 793	8. 8 6. 1 4. 9 5. 2	1, 353, 201 4, 897, 050 38, 020, 958	91. 0 70. 6 93. 3 94. 4	1, 486, 782 6, 932, 843 40, 757, 651	87, 390 15, 689 13, 945, 633 12, 739, 006 696, 501	5. 6 . 2 25. 5 56. 7	1, 574, 172 6, 948, 532 54, 703, 284
Iowa Kansas Kentucky Maryland	298, 294 68, 760 1, 673, 625	13. 3 8. 9 3. 2 48. 7	974, 471 390, 051 1, 500, 913	43. 5 50. 6 2. 9	9, 195, 119 969, 360 312, 441 49, 286, 683 865, 853	43. 2 40. 5 93. 9 51. 3	9, 744, 923 2, 242, 125 771, 252 52, 461, 221 1, 687, 909	696, 501 3, 236, 320 1, 249, 125 12, 665	23. 7 80. 8 2. 3	22, 483, 929 2, 938, 626 4, 007, 572 53, 710, 346 1, 700, 574
Michigan. Missouri. Montana (bituminous coal). Montana and Texas (lignite).	183, 780 11, 948 14, 818	16.0 .7 4.6	315 108, 136 25, 102 291, 195	.1 9.5 1.4 91.2	310, 460 853, 751 1, 761, 938 13, 434	99. 9 74. 5 97. 9 4. 2	310, 775 1, 145, 667 1, 798, 988 319, 447	1, 999, 621 1, 395, 943 76, 672	63. 6 43. 7 19. 4	310, 775 3, 145, 288 3, 194, 931 396, 119
New Mexico North Dakota (lignite) Ohio Oklahoma	490, 731 7, 161 316, 212 4, 402	39. 2 . 9 1. 4 . 4	250, 965 188, 754 154, 257 199, 891	20. 1 24. 2 . 7 19. 5	509, 424 585, 829 21, 533, 127 821, 428	40. 7 74. 9 97. 9 80. 1	1, 251, 120 781, 744 22, 003, 596 1, 025, 721	1, 527, 144 7, 315, 247 745, 387	66. 1 25. 0 42. 1	1, 251, 120 2, 308, 888 29, 318, 843 1, 771, 108
Pennsylvania. South Dakota (lignite) Tennessee. Texas (bituminous coal) Utah		14. 5 3. 4 13. 9 100. 0	3, 380, 755 4, 245 871, 749	2.8 96.6 12.4	100, 769, 853 5, 190, 016	82. 7 73. 7	121, 809, 905 4, 395 7, 043, 671 15, 482	8, 429, 778 66, 430 1, 600	6. 5 93. 8 (¹)	130, 239, 683 70, 825 7, 045, 271 15, 482
Otan Virginia Washington West Virginia Wyoning	16, 635 49, 747 244, 548 6, 853, 305 30, 800	.4 .3 13.4 4.9	160, 315 1, 471, 630 626, 537 678, 868 140, 127	3.9 8.0 34.2 .5 2.2	3, 899, 829 16, 916, 852 958, 074 131, 619, 456 6, 295, 843	95. 7 91. 7 52. 4 94. 6 97. 4	4,076,779 18,438,229 1,829,159 139,151,629 6,466,770	2, 717 12, 115 1, 098, 619 179, 560	(1) .7 .8 2.7	4, 076, 779 18, 440, 946 1, 841, 274 140, 250, 248 6, 646, 330
Total	32, 672, 276	7. 1	17, 895, 064	3.9	408, 510, 296	89. 0	459, 077, 636	55, 071, 609	10.7	514, 149, 245

<sup>1</sup> Less than 0.05 percent.

Table 23.—Number of coal-cutting machines in bituminous-coal and lignite mines, average output per machine, and percent of total product of underground mines cut by machines in the United States, by States, in 1941

	Number of c	oal-cutting ma	chines in use	Average out-	Percent of total produc
State	Permissible	Other	Total	put per ma- chine (net tons)	of under- ground mines cut by ma- chines
Alabama Arkansas Colorado Illinois Indiana Iowa Kansas Kentucky Maryland Michigan Missouri Montana: Bituminous coal Lignite New Mexico North Dakota (lignite) Ohlo Oklahoma Pennsylvania Tennessee Utah Virginia Washington West Virginia Wyoming	211 252 122 48 38 469 40 12 67 21 (1) 27 1 11 302 66 2, 134 41 89 117 49 897	328 59 2211 655 123 53 1,072 8 26 27 47 (1) 28 19 19 11 11 12 12 13 11 11 12 12 13 13 13 13 13 13 14 16 16 17 18 18 18 18 18 18 18 18 18 18	552 144 432 907 245 101 1,541 48 38 94 (1) 55 1 20 933 97 3,356 194 126 329 52 2,943 22,943	20, 961 9, 397 11, 336 41, 919 37, 531 9, 598 6, 126 31, 984 18, 039 8, 170 9, 082 25, 911 (1) 9, 262 1 29, 963 23, 963 23, 963 23, 963 24, 963 30, 951 51, 419 18, 425 44, 723 22, 326	76. ( 91. ( 93. ( 94. 4 43. 2 40. ( 93. 3 51. 3 97. 2 (1) 40. 7 171. 6 97. 9 80. 1 82. 7 73. 7 95. 7 95. 7 95. 7
Total, United States	5, 375	7, 233	12,608	32, 401	89.0

<sup>&</sup>lt;sup>1</sup> Montana (lignite) included with North Dakota.

Table 24.—Stripping operations of all types in the bituminous-coal and lignite fields of the United States, by States and counties, in 1941

[Returns for mines that recover coal both by stripping and by underground operations do not permit separating men engaged in stripping from those engaged in other work. For this reason, the figures of men employed represent all persons working at these mines, including those underground. The total tons produced by both methods at these mines are also shown]

		Numbe	r of power	shovels	Coal produc	ed (net tons)	Avei	age numbe	r of emplo	yees	Average		
State and county	Number of strip			All	Mined by	Total at	Under-	Suri	ace		number of days mines	Number of man- days	Average tons per man per
	pits	Steam	Electric	others	stripping	same mines	ground	In strip pits	All others	Total	were active	worked	day
Alabama: Blount, Jefferson, Marion, and Walker	8	10	1	3	238, 447	251, 623	19	141	40	200	253	50, 697	4. 96
Arkansas: Franklin and Johnson Sebastian	3 7	1 2		3 3	48, 331 39, 059	48, 331 41, 788	5	39 81	8 22	47 108	171 91	8, 019 9, 806	6. 03 4. 26
Total Arkansas	10	3		6	87, 390	90, 119	5	120	30	155	115	17, 825	5.06
Illinois: Crawford, Grundy, Hancock, Henry, Jackson, Knox, Living- ston, McDonough, Randolph, Saline, Schuyler, Will, and Williamson													
Saline, Schuyler, Will, and Williamson Fulton La Salle Perry St. Clafr Vermilion	7	1	25 17 2 14 5	30 7 9 4 8	5, 447, 128 4, 177, 304 174, 622 2, 875, 428 1, 002, 230 268, 921	5, 579, 422 4, 177, 304 174, 622 2, 875, 428 1, 002, 230 268, 921	52	797 357 64 389 107 37	628 387 42 300 69 36	1,477 744 106 689 176 73	240 244 165 241 252 124	354, 801 181, 565 17, 489 165, 735 44, 406 9, 024	15. 73 23. 01 9. 98 17. 35 22. 57 29. 80
Total Illinois	42	1	63	64	13, 945, 633	14, 077, 927	52	1, 751	1, 462	3, 265	237	773, 020	18. 21
Indiana: Clay	30	5	11	45	1, 925, 826	1, 925, 826		460	315	775	192	149, 097	12, 92
Daviess, Dubois, Knox, Owen, and Spencer Fountsin. Greene Pike. Sullivan.	6 6 14 17 8	7 4 2	10 14 3	9 7 13 19 8	460, 205 79, 658 1, 838, 455 4, 225, 665 729, 487	460, 205 79, 658 1, 838, 455 4, 225, 665 729, 487		82 34 275 483 139	74 11 407 485 158	156 45 682 968 297	195 162 207 210 212	30, 427 7, 275 141, 383 203, 370 63, 026	15. 12 10. 95 13. 00 20. 78 11. 57

Table 24.—Stripping operations of all types in the bituminous-coal and lignite fields of the United States, by States and counties, in 1941—Con.

	1	1	<del></del>		<u> </u>		<u> </u>						
	ĺ	Numbe	er of power	shovels	Coal produc	ed (net tons)	Ave	rage numb	er of emplo	yees	Average		
State and county	Number of strip pits			All	Mined by	Total at	Under-	Sur	face		number of days mines	Number of man- days	Average tons per man per
	F1.05	Steam	Electric	others	stripping	same mines		In strip pits	All others	Total	were active	worked	day
Indiana—Continued. Vermillion	4 7 4		2 4 8	3 9 5	241, 882 1, 216, 762 2, 021, 066	241, 882 1, 216, 762 2, 021, 066		76 166 170	56 223 253	132 389 423	121 187 261	15, 987 72, 836 110, 403	15. 13 16. 71 18. 31
Total Indiana	96	18	54	118	12, 739, 006	12, 739, 006		1, 885	1, 982	3, 867	205	793, 804	16.05
Iowa: Davis, Greene, Jasper, Keokuk, Monroe, Polk, Warren, and Webster.	10		2	8	49, 802	49, 802		59	35	94	99	9, 310	5. 35
Mahaska Marion Van Buren Wapello	11 21 4 5			20 26 4 9	272, 316 286, 014 15, 262 73, 107	272, 316 286, 744 15, 262 73, 107	2	96 139 15 22	61 38 5 29	157 179 20 51	191 191 145 179	29, 921 34, 184 2, 908 9, 125	9. 10 8. 39 5. 25 8. 01
Total Iowa	51		2	67	696, 501	697, 231	2	331	168	501	171	85, 448	8. 16
Kansas: Bourbon Cherokee Crawford Labette Linn and Osage	4 9 17 3 4	3 3 15 2 3	2 9 14	1 3 4 1 2	169, 351 1, 012, 045 1, 297, 457 16, 268 741, 199	169, 351 1, 012, 045 1, 297, 457 16, 268 741, 199		44 128 284 15 54	20 197 198 6 74	64 325 482 21 128	221 218 189 163 242	14, 156 70, 688 90, 918 3, 428 30, 957	11. 96 14. 32 14. 27 4. 75 23. 94
Total Kansas	37	26	27	11	3, 236, 320	3, 236, 320		525	495	1,020	206	210, 147	15. 40
Kentucky: Christian and Hopkins Laurel and Whitley	5 3	3 1	4	6 3	1, 236, 778 12, 347	1, 239, 253 12, 347	60	132 27	125 11	317 38	190 87	60, 322 3, 309	20. 54 3. 73
Total Kentucky	8	4	4	9	1, 249, 125	1, 251, 600	60	159	136	355	179	63, 631	19. 67
Missouri: Barton Bates Boone Callaway	5 7 3 4	4 5 1 3	2	2 3 4	221, 127 107, 997 14, 471 158, 238	107. 997 14. 471		61 65 18 48	31 7 2 14	92 72 20 62	173 167 162 287	15, 939 12, 026 3, 241 17, 823	13. 87 8. 98 4. 46 8. 88

Cedar, Clark, Dade, Howard, Jasper, Johnson, Lincoln, Ma- con, Moniteau, Monroe, Mor-													
con, Moniteau, Monroe, Morgan, Ralls, and Randolph Henry	16 16 7	3 10 8	6 7	15 4 1	849, 323 582, 348 66. 117	851, 931 583, 528 66, 117	4 3	209 201 51	135 106 14	348 310 65	186 172 150	64, 606 53, 255 9, 718	13. 19 10. 96 6. 80
Total Missouri	58	34	15	29	1, 999, 621	2, 003, 409	7	653	309	969	182	176, 608	11.34
Montana and Texas: Lignite	4 67	2 9	2 8	3 29	76, 672 1, 527, 144	76, 672 1, 527, 144		38 444	92	39 536	73 175	2, 847 93, 878	26. 93 16. 27
Ohio: Belmont Carroll Columbiana Coshocton	4 7 17 3	1 2 2		9 12 38 3	76, 400 294, 064 788, 508 24, 317	76, 400 302, 064 788, 508 53, 453	6 14	42 89 159 16	32 54 77 12	74 149 236 42	94 228 244 243	6, 928 33, 960 57, 555 10, 226	11. 03 8. 89 13. 70 5. 23
Gallia, Hocking, Holmes, Portage, and Wayne Harrison Jackson Jefferson Mahoning Muskingum Perry Stark Tuscarawas Vinton	6 9 5 12 9 3 4 18 29 8	1 5 3 3 3	4 1 1 2	10 18 3 17 16 5 9 46 42 8	127, 166 1, 492, 548 32, 881 2, 055, 170 387, 157 54, 062 256, 603 857, 984 770, 074 98, 313	127, 166 1, 657, 188 32, 881 2, 055, 170 387, 157 54, 062 260, 203 859, 876 770, 074 109, 869	125 	45 214 22 326 97 17 49 265 270 74	22 127 7 232 31 10 27 95 90 13	67 466 29 558 128 27 83 364 360 99	227 202 192 191 261 204 258 238 228 243	15, 219 94, 328 5, 564 106, 397 33, 355 5, 516 21, 413 86, 487 82, 119 24, 056	8. 36 17. 57 5. 91 19. 32 11. 61 9. 80 12. 15 9. 94 9. 38 4. 57
Total Ohio	134	28	12	236	7, 315, 247	7, 534, 071	168	1,685	829	2, 682	217	583, 123	12. 92
Oklahoma: Coal, Haskell, Rogers, Sequoyah, and Wagoner Craig	8 3	7 2	6	4 1	731, 744 13, 643	·			83	243 23	252 168	61, 252 3, 864	11. 95 3. 53
Total Oklahoma	11	9	6	5	745, 387	745, 387		183	83	266	245	65, 116	11. 45
Pennsylvania: AlleghenyArmstrongBeaverButler	32 9 9 10	6 1 2 1	2 1	39 14 26 17	843, 543 585, 166 844, 568 384, 788	1, 027, 928 862, 266 844, 568 403, 988	164 266 21	206 150 181 96	138 105 59 35	508 521 240 152	187 196 282 196	94, 941 102, 046 67, 629 29, 753	10. 83 8. 45 12. 49 13. 58
Cambria, Cameron, Clinton, Fulton, Lycoming, and McKean Center Clarion Clearfield Fayette Jefferson Lawrence Mercer Somerset Tioga	7 7 14 28 25 6 3 4 3	4 4 3 10 6 2	3	4 10 34 31 22 8 5 11 6	111, 727 234, 277 915, 661 707, 597 558, 934 314, 961 74, 085 231, 379 163, 179 94, 060	322, 133 395, 399 915, 661 796, 977 618, 622 327, 221 83, 996 237, 441 163, 179 94, 060	141 93 20 14 9	70 96 288 284 246 122 16 42 41 30	39 27 114 99 96 33 36 32 26 8	357 398 402 524 435 175 66 83 67 38	208 192 142 173 120 168 180 219 190	74, 250 76, 269 56, 899 90, 841 52, 103 29, 330 11, 872 18, 211 12, 700 6, 734	4. 34 5. 18 16. 09 8. 77 11. 87 11. 16 7. 08 13. 04 12. 85 13. 97

Table 24.—Stripping operations of all types in the bituminous-coal and lignite fields of the United States, by States and counties, in 1941—Con.

		Numbe	er of power	shovels	Coal produc	ed (net tons)	Ave	rage numb	er of emplo	yees	Average		
State and county	Number of strip			All	Mined by	Total at	Under-	Sur	face		number of days mines	Number of man- days	A-verage tons per man per
	pits	Steam	Electric	others	stripping	same mines		In strip pits	All others	Total	were active	worked	day
Pennsylvania—Continued.	-												
Washington Westmoreland	17 27	5	2	21 30	1, 662, 660 703, 193	1, 910, 054 807, 899	206 86	296 350	174 117	676 553	227 151	153, 647 83, 422	12. 43 9. 68
Total Pennsylvania	204	50	9	282	8, 429, 778	9, 811, 392	1, 543	2, 514	1, 138	5, 195	185	960, 647	10. 21
South Dakota: Lignite	8			7	66, 430	66, 430		44	7	51	195	9, 962	6. 67
Brooke	7			16	517, 888	517, 888		97	63	160	159	25, 383	20. 40
galia	5 4 3	1 2		10 6 4	180, 209 152, 027 248, 495	695, 721 152, 027 305, 026	183 66	57 49 45	80 28 66	320 77 177	252 78 205	80, 560 6, 015 36, 300	8. 64 25. 27 8. 40
Total West Virginia	19	3		36	1, 098, 619	1, 670, 662	249	248	237	734	202	148, 258	11. 27
Wyoming: Campbell, Carbon, Converse, and Sheridan Other States 1	5 7	2 1	2 5	6	179, 560 1, 440, 729	179, 560 1, 490, 011	44	56 84	16 29	• 72 157	221 225	15, 942 35, 270	11. 26 42. 25
Total United States	769	200	210	911	55, 071, 609	57, 448, 564	2, 149	10, 861	7, 054	20,064	204	4, 086, 223	14. 06

<sup>&</sup>lt;sup>1</sup> Includes Colorado, Maryland, Montana (bituminous coal), Tennessee, Virginia, and Washington.

Table 25.—Summary of operations of power strip pits proper in the bituminous-coal and lignite fields of the United States, by States, in 1941

		Number	of power	shovels			Aver-	Aver-
State	Num- ber of strip pits	Steam	Elec- tric	All others	Mined by stripping <sup>1</sup> (net tons)	Num- ber of men em- ployed	age num- ber of days mines were active	age tons per man per day
Power strip pits proper: Alabama Arkansas Illinois Indiana Iowa Kansas Kentucky Missouri North Dakota (lignite) Ohio Oklahoma Pennsylvania South Dakota (lignite) West Virginia Other States 3	5 7 41 90 46 34 7 49 288 125 11 161 4 4 17	9 3 1 18 26 4 34 9 27 9 33	1 60 54 2 27 4 15 8 8 12 6 6	1 6 64 118 67 11 7 7 28 29 227 5 245 7 34 8	235, 112 836, 384, 382 12, 727, 256 688, 457 3, 230, 712 1, 202, 089 1, 978, 812 1, 500, 711 7, 121, 307 7, 543, 594 63, 372 1, 93, 675 1, 673, 438	166 145 3,063 3,853 479 1,007 261 924 450 2,379 266 3,044 43 389 196	267 113 228 205 174 206 230 184 193 218 245 174 210 173 202	5. 31 5. 25 18. 41 16. 09 8. 26 15. 57 20. 05 11. 67 17. 26 13. 70 11. 45 14. 23 7. 01 16. 23 42. 23
Total Horse stripping operations Mines combining stripping and underground methods in the	637 75	180	204	857 54	53, 284, 375 113, 726 1, 673, 508	16, 665 240 4 3, 159	205 112	15. 59 4. 22
same operations 3	769	200	210	911	55, 071, 609	120, 064	1 204	4 14. 08

1 Excludes coal produced by underground mining conducted in the same operation.
2 Includes Colorado, Maryland, Montana (bituminous coal and lignite), Tennessee, Texas (lignite), Virginia, and Wyoming.
3 Includes operations in Alabama, Arkansas, Illinois, Iowa, Kentucky, Missouri, Ohio, Pennsylvania, Washington, and West Virginia, in which the output was obtained by both methods. In addition to the 1,673,608 tons produced by stripping. this group of 57 mines obtained 2,376,955 tons by underground methods, their total production by both methods being 4,050,463 tons.
4 Includes data on underground mining conducted in the same operation.

### POWER DRILLING

Table 26.—Summary of operations of underground bituminous-coal and lignite mines in the United States where shot holes were power-drilled, in 1941

	Numb mines				Nu	nber of p	ower o	irills			Net tons	produced	in working holes were	Total prod	uction from	mines using
	power			Elec	tric			Comp	oressed a	r	power-dr	illed	notes were	power	drills (net	tons)
State	In coal and coal and rock	In rock only	In coal only	In coal and rock	In rock only	Total	In coal only	In coal and rock	In rock only	Total	Electric drills	Com- pressed air drills	Total	In coal and coal and rock	In rock only	Total
Alabama Arkansas Colorado Illinois Indiana Iowa Kentucky Maryland Michigan Missouri Montana (bituminous coal	48 10 58 114 26 7 177 4 5	9 17 2 2 1 1 28 3 1 10	547 20 216 936 146 17 789 18 5	286 87 65 38 3 105 2 5	9 17 3 9 4 80 4 3 5	842 37 306 1,010 188 20 974 24 13	1 3 1 5 5	2	134 42 23 20 7 7 108 1 1	135 47 23 21 7 5 113 1	8, 813, 263 238, 682 3, 530, 576 34, 825, 384 8, 077, 117 169, 126 30, 184, 979 353, 059 71, 893	81, 925 38, 118 11, 278 31, 593 260, 922	8, 895, 188 276, 800 3, 530, 576 34, 836, 662 8, 077, 117 200, 719 30, 445, 901 353, 059 71, 893	12, 199, 919 341, 078 5, 126, 755 35, 559, 552 8, 090, 996 543, 320 39, 179, 108 671, 402 209, 178	815, 443 657, 062 306, 830 250, 463 42, 926 5, 126, 920 111, 096 22, 946 292, 550	13, 015, 362 998, 140 5, 433, 585 35, 810, 015 8, 133, 922 543, 320 44, 306, 028 782, 498 232, 124 292, 550
and lignite) New Mexico Ohio Pennsylvania Tennessee Utah Virginia West Virginia West Virginia Wyoming Other States 1	47	1 5 59 6 12 56	47 22 213 901 81 106 158 71 1,304 365 40	91 318 9 2 2 19 229 21 11	25 139 7 1 16 81	47 22 329 1, 358 97 109 174 90 1, 614 387 51	1 73 10 34 13	7 1 12	1 11 9 445 22 9 42 27 304 7	1 11 13 562 22 9 44 112 314 41	1, 691, 723 298, 725 13, 003, 117 46, 225, 900 2, 059, 767 3, 733, 735 7, 357, 426 526, 448 62, 842, 339 6, 208, 438 629, 277	122, 145 4, 350, 213 	1, 691, 723 298, 725 13, 125, 262 50, 576, 113 2, 059, 767 3, 733, 735 7, 408, 381 1, 362, 285 63, 242, 975 6, 319, 431 706, 552	1, 691, 723 520, 136 14, 475, 879 70, 830, 803 3, 554, 859 3, 770, 246 9, 449, 307 1, 619, 978 88, 976, 639 6, 333, 492 820, 413	310, 753 963, 347 19, 529, 351 1, 137, 145 3, 631, 035 22, 385, 172 30, 144	1, 691, 723 830, 889 15, 439, 226 90, 360, 154 4, 692, 004 3, 770, 246 13, 080, 342 1, 619, 98 111, 361, 81 6, 333, 492 850, 557
Total United States	1, 053	213	6,002	1, 291	404	7, 697	260	23	1, 219	1, 502	230, 840, 974	6, 371, 890	237, 212, 864	303, 964, 783	55, 613, 183	359, 577, 96

<sup>&</sup>lt;sup>1</sup> Alaska, Kansas, North Dakota (lignite), Oklahoma, and South Dakota (lignite).

下記法官 原本人名 以公子不以

# MECHANICAL LOADING IN UNDERGROUND BITUMINOUS-COAL AND LIGNITE MINES

Mechanical loading devices used in underground bituminous-coal and lignite mines are divided into two general classes: Those that practically eliminate hand-shoveling, which are known as mobile loaders, scrapers, and self-loading conveyors or duckbills; and those that greatly reduce the labor of hand-shoveling, which are known as

hand-loaded face conveyors and pit-car loaders.

The first systematic record of mechanical loading began in 1923 when 60 mines loaded 1,879,726 net tons (0.3 percent of the underground output) with the aid of mechanical loading devices. Ten years later (in 1933) mechanical loading had spread to 283 mines, and 37,820,461 net tons (12 percent of the total underground output) were loaded mechanically. Since 1933 the proportion mechanically loaded has increased each year and in 1941 it amounted to 41 percent of the total underground bituminous coal and lignite mined in the United States.

During the 3 years 1939-41 the percentage loaded by each class has been fairly constant, the mobile loaders, scrapers, and duckbills handling about 76 percent and the hand-loaded conveyors and pit-car

loaders about 24 percent of the total.

Detailed statistics on mechanical loading given in the following tables (27 to 33, inclusive) pertain to underground coal mines and do not include strip mines or equipment used for handling coal on the surface. All tonnage figures on coal mechanically loaded include the initial phase of loading only; for instance, if conveyors were used in conjunction with mobile loaders, the tonnage is shown under mobile loading machines and not under conveyors.

Sales of mechanical loading equipment in 1942.—The estimated capacity of mechanical loading equipment sold for underground use in all coal mines was 7.7 percent less in 1942 than in 1941. This decrease was due in part to some of the manufacturers devoting a portion of their facilities to war work. Table 27 shows the sales reported, by type of equipment, and the number of manufacturers

reporting for 1935-42.

Sales of conveyors to bituminous-coal and lignite mines in 1942 totaled 1,167 units. This figure excludes duckbills, which have been included in all previous years. Therefore, the figures for 1942 are not comparable with those for 1941 or earlier years. By excluding sales of duckbills, some of the overlapping sales of conveyors are eliminated. For instance, in 1940 there were 2,919 conveyors, including those hand-loaded and those equipped with duckbills, in active use at bituminous-coal and lignite mines, as reported by mine operators. By adding 1940 conveyor and duckbill sales of 1,573 units, 4,492 units appeared available for use in 1941, whereas the actual number reported in use by mine operators was 3,595, or 897 less. This difference represents idle or worn-out and obsolete equipment, duplications in reporting sales, and a small number of conveyors used in conjunction with mobile loaders.

The number of mobile loaders, scrapers, and conveyors shipped into the various States and groups of States in 1942 and the number

of units in actual use in 1941 are shown in table 29. Pennsylvania bituminous-coal mines received the largest number of mobile loaders sold in 1942; West Virginia was in second place, and Alabama and Kentucky tied for third place.

All of the 15 scraper units sold in 1942 went to the bituminous-coal

mines

Conveyor sales in 1942, in relation to the number in actual use in 1941, were greater in the Middle Western States than in any other

regions.

Detailed statistics of mechanical loading in bituminous-coal and lignite mines in 1940 and 1941, by types of equipment.—During 1941, the latest year for which records are available, the approximate percentage of the tonnage loaded by each type of equipment was as follows: Mobile loaders, 68; hand-loaded conveyors, 21; duckbills, 8;

pit-car loaders, 2; and scrapers, 1.

Mobile loaders have handled more coal than any other type of mechanical loading device, and since 1934 they have loaded more than all the other types together. The most common method of employing mobile loaders is for loading coal directly into mine cars, but they also load into shuttle cars (rubber-tired trackless haulage units) and onto conveyors. During 1941, 86 percent of the bituminous coal and lignite handled by mobile loaders was loaded directly into mine cars, 11 percent into shuttle cars, and 3 percent onto conveyors.

In the underground bituminous-coal and lignite mines, 1,985 mobile loaders handled 126,478,074 net tons in 1941, an average of 63,717 tons per mobile loader per year; hand-loaded face conveyors averaged 14,440; duckbills, 18,932; pit-car loaders, 5,679; and scrapers, 11,832

per year per unit for the same period (see tables 30 and 31).

Mechanical loading, by States.—Illinois led all other States in underground tonnage mechanically loaded from 1928 to 1938; then it was passed by West Virginia in 1939. In 1941, West Virginia produced 57,511,968 net tons of mechanically loaded coal, followed by Pennsylvania with 35,164,964 net tons, Illinois with 33,273,976, Ohio with 11,943,605, and Kentucky with 11,496,678. These five States produced 80 percent of the total output of mechanically loaded bituminous coal in the United States in 1941.

Detailed data, by States, on number of mines and machines and production of mechanically loaded coal compared with total production at mines using mechanical loading devices are given in table 31. Comparative changes in underground mechanical loading in 1940-41,

by States, are shown in table 32.

Table 33 gives bituminous coal and lignite mined by stripping compared with underground hand-loaded and machine-loaded tonnage, by States, for 1941.

Table 27.—Units of mechanical loading equipment sold to bituminous-coal, anthracite, and lignite mines for underground use in the United States, as reported by manufacturers, 1935-42, inclusive

	1935	1936	1937	1938	1939	1940	1941	1942	Change, 1942 from 1941 (percent)
Type of equipment:  Mobile loaders Scrapers 1 Conveyors 2 Pit-car loaders	115 22 681 28	344 28 994 11	292 29 1,095 32	241 10 990 139	292 26 1, 311 2	233 39 1, 762 3	368 11 2, 130 10	352 29 3 1, 491 2	-4.3 +163.6 (3) -80.0
Total, all types	846	1, 377	1, 448	1, 380	1, 631	2, 037	2, 519	3 1,874	(3)
Number of manufacturers reporting	28	28	28	29	31	32	32	28	

Table 28.—Sales of mechanical loading equipment in the United States in 1942 compared with total number of machines in active use in preceding years

	N	lumber	r of ma		in acti e opera		as repo	orted b	У	Num- ber of ma- chines sold as report-
	1933	1934	1935	1936	1937	1938	1939	1940	1941	ed by manu- factur- ers in 1942
Bituminous-coal and lignite mines: Mobile loading machines. Scrapers. Pit-car loaders. Conveyors equipped with duck-	523 93 2, 453	534 119 <b>2,</b> 288	657 78 <b>2,</b> 098	980 106 1,851	(1)	1, 405 117 1, 392	131	116	1, 985 109 607	
bills and other self-loading heads. Hand-loaded conveyors—number of units  Anthracite mines (Pennsylvania):	132 525	157 574	179 670		``	346 1,526		656 2, 263	788 2, 807	(2) 2 1, 167
Mobile loading machines Scrapers Pit-car loaders Conveyors equipped with duck-	18 455 19	14 517 25	507 22	(3) 3 504 (5)	539 (4)	(4) 545 (4)	(4) 535 (4)	(3) 3 547 (5)	(3) 3 505 (5)	14
bills and other self-loading heads Hand-loaded conveyors—number of units	12 940	13 1,338	30 1, 563	. '′	(4) 4 1,855	(4) 4 1,831	(4) 4 1,997	(5) 5 <b>2,1</b> 89	(5) 5 <b>2,4</b> 32	<sup>(2)</sup> 2 324

<sup>&</sup>lt;sup>1</sup> Reported as scrapers or scraper haulers and hoists.
<sup>2</sup> Includes hand-loaded conveyors and those equipped with duckbills and other self-loading heads. Sales of both loading heads and shaker conveyors are counted for 1935–41, inclusive, but the figure for 1942 does not include loading heads separately; see text for additional explanation.
<sup>3</sup> Not comparable with previous years; see footnote 2.

Data for 1937 not available for bituminous-coal and lignite mines.
 Conveyors equipped with duckbills are included with hand-loaded conveyors. In sales for 1942 loading heads were not counted as a separate unit.
 Mobile loading machines are included with scrapers.
 Mobile loading machines, pit-car loaders, and conveyors equipped with duckbills and other self-loading heads are included with hand-loaded conveyors.
 Pit-car loaders and conveyors equipped with duckbills and other self-loading heads are included with hand-loaded conveyors.

からからない これではないないないないかられていないから

Table 29.—Comparison of mobile loaders, scrapers, and conveyors in actual use in bituminous-coal and lignite mines in the United States in 1941 with sales reported in 1942, by States and regions

	Mobile	loaders	Scra	pers	Conve	yors 1
State and region	In use in 1941	Sales in 1942	In use in 1941	Sales in 1942	In use in 1941	Sales in 1942
Northern Appalachian States: Pennsylvania Maryland	373	116	26	2	734 28	191
Ohio Michigan	122	31			153	75
Southern Appalachian States: Alabama Kentucky Tennessee	29 142 3	32 32	48	4	330 284 90	100 81 23
West Virginia Virginia	464 41	75 2	5	3	1,077 111	485 45
Middle Western States: Illinois	540 135 136	28 13 23	30	6	20 14 749	32 2 133
Total	1,985	352	109	15	3, 595	1, 167

<sup>&</sup>lt;sup>1</sup>Includes hand-loaded conveyors and conveyors equipped with duckbills or other self-loading devices.

<sup>1</sup>Includes Arkansas, Colorado, Iowa, Montana, New Mexico, North Dakota, Oklahoma, Utah, Washington, and Wyoming.

Table 30.—Bituminous coal and lignite mechanically loaded underground in the United States, 1940–41, by types of machines

	1940	)	1941	
Type of machine	Net tons	Percent	Net tons	Percent
Mobile loading machines.  Scraper loaders.  Conveyors equipped with duckbills or other self-loading	100, 961, 745 1, 255, 396	68. 3 . 8	126, 478, 074 1, 289, 710	67. 8 . 7
devicesPit-car loaders	10, 361, 694 3, 979, 209 31, 312, 208	7. 0 2. 7 21. 2	14, 918, 583 3, 447, 028 40, 533, 855	8.0 1.8 21.7
Grand total loaded mechanically	147, 870, 252	100.0	186, 667, 250	100.0

	1	Tumber	r of min	ies		Nun	ber of mac	hines		Productio	n mechanic (net tons)	ally loaded	Total prod	uction at m ading devic	ines using n es (net tons	nechanical )
State	Using load- ing ma- chines only <sup>1</sup>	Using con- vey- ors only 2	Using both loading machines and conveyors	Total	Mobile load- ing ma- chines	Scrap- ers	Conveyors equipped with duckbills and other self- loading devices	Pit- car load- ers	Hand- loaded con- vey- ors <sup>3</sup>	Loaded by machines 1	Handled by con- veyors <sup>2</sup>	Total	Mines using loading machines only <sup>1</sup>	Mines using conveyors only 2	Mines using both loading machines and conveyors	Total
Alabama. Arkansas. Colorado. Illinois. Indiana. Iowa. Kentucky. Maryland Michigan. Montana (bituminous	15 2 24 49 21 1 54	24 26 25 7 4 4 27 4	6 5 12 3	45 28 54 68 28 5 92 4	29 23 540 135 3 142	48 12	120 6 7	35 4 187 21 29	328 77 109 14 7 19 154 28 5	2, 006, 569 (4) 2, 090, 978 32, 173, 463 8, 070, 401 (4) 9, 631, 877	3, 841, 428 (4) 851, 409 1, 100, 513 189, 901 (4) 1, 864, 801 (4) (4)	5, 847, 997 1, 053, 603 2, 942, 387 33, 273, 976 8, 260, 302 174, 958 11, 496, 678 (4)	4, 354, 383 (4) 3, 137, 786 27, 470, 071 7, 757, 932 (4) 13, 084, 681	4, 934, 111 (4) 1, 124, 268 477, 562 98, 267 (4) 6, 460, 043 (4) (4)	2, 641, 677 605, 063 6, 453, 479 660, 011 4, 243, 534	11, 930, 171 1, 053, 603 4, 867, 117 34, 401, 112 8, 516, 210 506, 760 23, 788, 258 (*)
Montana (bituminous coal)  New Mexico  North Dakota (lignite)  Ohio  Oklahoma	6 3 1 22	10 11	1 4	7 3 1 36 11	41 7 3 122	10	2 96	6	57 29	(4) (4) (4) 10, 860, 007	1, 083, 598 421, 973	1, 621, 024 (4) (4) 11, 943, 605 421, 973	(4) (4) (4) (11, 854, 828	743, 455 429, 344	(4) 1, 100, 767	1, 653, 089 (4) (4) 13, 699, 050 429, 344
Pennsylvania	3 7 15	57 20 7 9 7 99 7	25 2 3 3 3 60 4	147 25 17 27 11 260 27	373 36 41 1 464 22	26 5 8	40 8 16 11 8 144 198	196  102 26	694 82 40 100 82 933 49	23, 807, 589 144, 414 2, 878, 639 2, 458, 841 94, 760 40, 556, 952 5, 517, 515	11, 357, 375 1, 276, 989 488, 209 1, 434, 171 923, 632	35, 164, 964 1, 421, 403 3, 366, 848 3, 893, 012 1, 018, 392 57, 511, 968 6, 177, 445	37, 245, 474 (4) 2, 582, 870 5, 752, 724 385, 441 48, 204, 871 5, 085, 998	2, 797, 162 708, 399 1, 806, 068 932, 559	10, 864, 729 (4) 438, 927 830, 105 21, 497, 034 879, 834	63, 086, 657 3, 582, 737 3, 730, 196 8, 388, 897 1, 318, 000 91, 327, 765 6, 266, 034
Undistributed: East of Mississippi River West of Mississippi River										2, 394, 362	441, 813 1, 090, 125	441, 813 634, 902	3, 083, 239	710, 388 1, 412, 897	361, 844	710, 388 858, 953
Total: 1941	372	349 315 +10.8	139 124 +12.1	897 811 +10.6	1, 985 1, 720 +15. 4	109 116 -6.0	788 656 +20. 1	607 697 -12. 9	2,807 2,263 +24.0	142, 686, 367 112, 578, 835 +26. 7	43, 980, 883 35, 291, 417 +24. 6	186, 667, 250 147, 870, 252 +26. 2	170, 000, 298 137, 883, 289 +23. 3		50, 577, 004 43, 623, 716 +15. 9	280, 114, 341 241, 381, 132 +16. 0

<sup>&</sup>lt;sup>1</sup> Includes those mines in which all of the tonnage mechanically loaded was obtained with machines that substantially eliminate hand shoveling; that is, mobile loaders, scrapers, and conveyors equipped with duckbills and other self-loading heads. Some mines in this class also use conveyors in conjunction with mobile loaders to perform the initial phase of transportation.

<sup>2</sup> Includes those mines in which all the tonnage mechanically loaded was obtained with hand-loaded conveyors and pit-car loaders.

Number of units.
 Included under "Undistributed" to avoid disclosing individual operations.

Table 32.—Comparative changes in underground mechanical loading of bituminous coal and lignite by principal types of machines in the United States, by States, 1940-41

		1940 (net tons)			1941 (net tons)		Perc	ent handled	by each clas	:S
State	Loaded by	Handled by		Loaded by	Handled by		19	40	1:	941
	machines 1	conveyors 3	Total	machines 1	conveyors 2	Total	Loaded by machines 1	Handled by conveyors <sup>2</sup>	Loaded by machines 1	Handled by conveyors 2
Alabama Arkansas Colorado	1, 603, 194 (³) · 1, 868, 794	3, 401, 717 (3) 683, 932	5, 004, 911 945, 052 2, 552, 726	2, 006, 569 (³) 2, 090, 978	3, 841, 428 (³) 851, 409	5, 847, 997 1, 053, 603 2, 942, 387	32. 0 (3) 73. 2	68. 0 (3) 26. 8	34. 3 (3) 71. 1	(3) 65. 7 28. 9
Illinois Indiana Iowa	28, 156, 030 7, 176, 040	1, 364, 457 230, 880 (³)	29, 520, 487 7, 406, 920 132, 947	32, 173, 463 8, 070, 401 ( <sup>3</sup> )	1, 100, 513 189, 901 (3)	33, 273, 976 8, 260, 302 174, 958	95. 4 96. 9	3. 1	96. 7 97. 7 (3) 83. 8	3.3
Kentucky Maryland Michigan Montana (bituminous coal)		1, 656, 208 (3) (3) (3)	7, 150, 554 (3) (3) 1, 511, 123	9, 631, 877	1, 864, 801 (3) (3) (3)	11, 496, 678 (3) (3) 1, 621, 024	76.8	23. 2 100. 0 100. 0	83.8	16. 2 100. 0 100. 0 (3)
New Mexico	(3) (3) 7, 750, 819	(3) 493, 023 (3)	(3) (3) 8, 243, 842 422, 692	(3) (3) (3) (3) 10, 860, 007	1, 083, 598 421, 973	(3) (3) 11, 943, 605 421, 973	(3) (3) 100. 0 94. 0 (3)	(3) (3) 6.0	100. 0 100. 0 90. 9	9. 1 100. 0
Pennsylvania Tennessee Utah	(3) 18, 031, 402 93, 601 2, 519, 675	9, 203, 654 622, 215 353, 285	27, 235, 056 715, 816 2, 872, 960	23, 807, 589 144, 414 2, 878, 639	11, 357, 375 1, 276, 989 488, 209	35, 164, 964 1, 421, 403 3, 366, 848	66. 2 13. 1 87. 7	33. 8 86. 9 12. 3	67. 7 10. 2 85. 5	32. 3 89. 8 14. 5
Virginia Washington West Virginia Wyoming Undistributed;	1, 996, 634 62, 000 30, 878, 128 4, 799, 234	1, 111, 788 733, 494 13, 100, 403 571, 885	3, 108, 422 795, 494 43, 978, 531 5, 371, 119	2, 458, 841 94, 760 40, 556, 952 5, 517, 515	1, 434, 171 923, 632 16, 955, 016 659, 930	3, 893, 012 1, 018, 392 57, 511, 968 6, 177, 445	64. 2 7. 8 70. 2 89. 4	35. 8 92. 2 29. 8 10. 6	63. 2 9. 3 70. 5 89. 3	36. 8 90. 7 29. 5 10. 7
East of Mississippi River West of Mississippi River	2, 148, 938	388, 831 1, 375, 645	388, 831 512, 769	2, 394, 362	441, 813 1, 090, 125	441, 813 634, 902	(4) (4)	(4) (4)	(4)	(4) (4)
Total	112, 578, 835	35, 291, 417	147, 870, 252	142, 686, 367	43, 980, 883	186, 667, 250	76. 1	23. 9	76. 4	23. 6

Includes mobile loaders, scrapers, and duckbills.
Includes hand-loaded conveyors and pit-car loaders.
Included under "Undistributed" to avoid disclosing individual operations.
Included in total; percentage by types not given because State groups are not comparable.

Table 33.—Bituminous coal and lignite in the United States mined underground and from strip pits and method of loading underground, in net tons, by States, in 1941

		1M.	lined undergro	und	Grand
State	Mined by stripping	Hand-loaded	Machine- loaded	Total	total production
Alabama Arkansas Colorado Illinois Indiana Lowa Kansas Kentucky Maryland Michigan Missouri Montana (bituminous coal) Montana (bituminous coal) Montana, South Dakota, and Texas (lignite) New Mexico North Dakota (lignite) Ohio Oklahoma Pennsylvania Temnessee Texas (bituminous coal) Utah Virginia Washington West Virginia Wyoming Other States 2 Undistributed	15, 689 13, 945, 633 12, 739, 006 696, 501 3, 236, 320 1, 249, 125 12, 665 1, 999, 621 1, 395, 943 143, 102 1, 527, 144 7, 315, 247 7, 45, 387 8, 429, 78 1, 600 2, 717 12, 115 1, 098, 619 179, 560	9, 378, 079 433, 179 3, 990, 483 67, 483, 667 1, 484, 621 2, 067, 167 771, 252 40, 964, 543 (1) 11, 145, 667 177, 964 323, 842 (1) 10, 050, 991 603, 748 86, 644, 941 15, 622, 268 165, 482 709, 931 4, 545, 217 810, 767 81, 639, 661 289, 325 293, 772 2, 954, 833		323, 842 1, 251, 120 781, 744 22, 003, 596 1, 025, 721 121, 809, 905 7, 043, 671 15, 482 4, 076, 779 18, 438, 229 1, 829, 159 139, 151, 629 6, 466, 770 293, 777	15, 464, 523 1, 574, 172 6, 948, 532 54, 703, 284 22, 483, 929 2, 938, 626 4, 007, 572 53, 710, 346 1, 700, 574 310, 773 3, 145, 288 3, 194, 931 466, 944 1, 251, 120 2, 308, 888 29, 318, 843 1, 771, 108 130, 239, 683 7, 045, 271 15, 482 4, 076, 779 18, 440, 946 1, 841, 274 140, 250, 248 6, 646, 330 293, 777
Total	55, 071, 609	272, 410, 386	186, 667, 250	459, 077, 636	514, 149, 245

<sup>&</sup>lt;sup>1</sup> Included under "Undistributed."

#### MECHANICAL CLEANING

Complete annual data on the mechanical cleaning of bituminous coal in the United States were first gathered for 1927; during that year 5.3 percent of the total production was cleaned by wet or pneumatic methods. This percentage increased annually, and in 1941 amounted to 23 percent or 117,469,857 net tons of clean coal. Tables 34, 35, 37, and 38 include data on all coal mined in the United States (excluding Alaska) except Pennsylvania anthracite. Tables 36 and 39 are upon the same basis but do not include consumer-operated plants. There are no mechanical cleaning plants at lignite mines.

For purposes of comparison, data on Alaska, which had one wetwashing installation, have not been included in the following tables. This one plant produced 52,754, 64,567, and 69,665 net tons of cleaned

coal in 1939, 1940, and 1941, respectively.

Consumer-operated plants include plants owned by steel companies which receive coal from various mines (but usually from affiliated companies), clean it, and then consume it directly at the plant.

Table 34 compares bituminous coal cleaned in 1940 and 1941, by method of cleaning. Both wet and pneumatic methods increased in

1941 over 1940.

Mechanical cleaning, by types of equipment.—The tonnage of bituminous coal cleaned by wet-washing methods reached 100,307,969 net tons in 1941—an increase of 15 percent over 1940. The quantity

<sup>&</sup>lt;sup>2</sup> Includes Alaska, Arizona, Georgia, Idaho, and Oregon.

cleaned by pneumatic methods was 17,161,888 net tons—also a

15-percent increase over 1940.

Table 35 compares the number of cleaning plants and the net tons of cleaned coal, by types of equipment, for 1940 and 1941. During 1941, 380 wet-washing and 80 pneumatic cleaning plants were in operation. Forty-four tipples used both wet and dry methods at the same plant; deducting these duplications gives a net total of 416 plants that cleaned coal in 1941 compared with 386 in 1940.

Wet methods of cleaning coal include piston- or common-type jigs, Baum-type jigs, concentrating tables, launders and upward-current classifiers, and combinations of jigs with concentrating tables and jigs with launders or upward-current classifiers. Baum-type jigs cleaned approximately 40 percent of the coal cleaned by wet methods during

1941.

Pneumatic methods of coal cleaning include air tables, air flow, air sand, and any combinations of these three methods. During 1941, air tables cleaned over 50 percent of the coal cleaned by pneumatic

methods.

Table 36 lists the total production in 1940 and 1941 at bituminous-coal mines that have cleaning plants, by types of equipment. This table shows that 185,398,504 net tons were produced at mines with cleaning plants in 1941, but the cleaned coal obtained at these mines totaled 108,218,314 net tons (see table 38) or 58 percent of the total produced. The remainder of the output (42 percent) presumably represents the larger sizes, which are generally hand-picked.

Coal cleaning, by States.—In volume of total tonnage of bituminous coal mechanically cleaned in 1941, Pennsylvania led; West Virginia, Illinois, Alabama, and Indiana followed in the order named. These five States supplied 98,839,286 tons (84 percent) of the total. Table 37 shows the number of plants in operation, net tons of clean coal, and percentage of State output mechanically cleaned in 1940 and 1941.

Results of operations and the relation between raw coal, clean coal, and refuse at bituminous-coal-cleaning plants by States in 1941 are

shown in table 38.

Methods of mining at mines served by cleaning plants.—Mechanical loading, both in underground mines and strip pits, appears to be closely related to mechanical cleaning. Table 39 shows the mining methods at mines that have cleaning plants. Production of coal from strip mines in 1941 was 55,071,609 tons (see table 33); 24,773,543 tons (45 percent) came from strip mines having mechanical cleaning tipples. There were 186,667,250 tons of underground coal loaded mechanically in 1941, of which 93,373,789 tons (50 percent) passed through tipples equipped with mechanical cleaning devices. Handloaded underground coal production in 1941 totaled 272,410,386 tons, of which 25 percent passed through tipples equipped with cleaning plants.

The state of the s

Table 34.—Bituminous coal mechanically cleaned by wet and pneumatic methods, in the United States, in net tons of clean coal, 1940-41 1

Method of cleaning	1940	1941	Change, 1941 from 1940 (percent)
By wet methods: At mines. At consumer-operated cleaning plants.	78, 475, 302	91, 056, 426	+16.0
	8, 750, 220	9, 251, 543	+5.7
Total wet methodsBy pneumatic methods	87, 225, 522	100, 307, 969	+15.0
	14, 979, 664	17, 161, 888	+14.6
Grand total	102, 205, 186	117, 469, 857	+14.9

<sup>&</sup>lt;sup>1</sup> Figures do not include Alaska, which had 1 wet-washing installation.

Table 35.—Bituminous coal cleaned in the United States, by types of equipment in actual operation, 1940-41 1

[Coal cleaned and plants operated by consumers at central washeries in Colorado and Pennsylvania are included]

Type of equipment	Plan		Net tons o	f clean coal		Percent cleaned by each type		
Type of equipment	1940	1941	1940	1941	1940	1941		
Wet methods: Jigs. Concentrating tables	186 13	201 13	46, 999, 035 2, 330, 413	53, 216, 901 2, 510, 186	46.0 2.3	45. 8 2. 2		
Jigs in combination with concentrating tables  Jigs in combination with launders and	16	20	2, 765, 237	4, 364, 220	2. 7	3. 7		
upward-current classifiers Launders and upward-current classifiers	11 124	11 135	4, 408, 148 30, 722, 689	5, 446, 245 34, 770, 417	4. 3 30. 0	4. 6 29, 6		
Total wet methodsPneumatic methods	350 77	380 80	87, 225, 522 14, 979, 664	100, 307, 969 17, 161, 888	85. 3 14. 7	85. 4 14. 6		
Grand total	2 427	2 460	102, 205, 186	117, 469, 857	100.0	100.0		

Table 36.—Total production of all coal at bituminous mines in the United States having cleaning plants, in net tons, 1940-41 1

[Does not include any estimate for mines that may ship to consumer-operated plants]

Type of equipment	1940	1941	Change, 1941 from 1940 (per- cent)
Wet methods: Jigs Concentrating tables Jigs in combination with concentrating tables Jigs in combination with launders and upward-current	75, 391, 008	85, 683, 303	+13.7
	1, 733, 048	1, 927, 109	+11.2
	3, 385, 168	5, 097, 435	+50.6
classifiers	7, 026, 222	8, 325, 444	+18.5
Launders and upward-current classifiers	56, 412, 328	69, 351, 140	+22.9
Total wet methodsPneumatic methods	143, 947, 774	170, 384, 431	+18.4
	41, 129, 603	45, 471, 216	+10.6
Grand totalLess duplication <sup>2</sup>	185, 077, 377	215, 855, 647	+16.6
	23, 405, 810	30, 457, 143	+30.1
Net total	161, 671, 567 460, 597, 6 <b>5</b> 6 35. 1	185, 398, 504 513, 910, 285 36. 1	+14.7 +11.6

Figures do not include Alaska, which had 1 wet-washing installation.
 Mines using both wet and pneumatic methods.
 For historical comparison, the United States production figures include lignite. Alaska is not included in total production.

Figures do not include Alaska, which had 1 wet-washing installation.
 Number of plants using both wet and pneumatic methods was 41 in 1940 and 44 in 1941.

Table 37.—Bituminous coal mechanically cleaned by wet and pneumatic methods in the United States, by States, 1940-41 1

[Coal cleaned and plants operated by consumers at central washeries in Colorado and Pennsylvania are

State		its in ation	Net tons of	clean coal	Perce State o mechan clean	utput
	1940	1941	1940	1941	1940	1941
Alabama Colorado Illinois Indiana Kansas Kentucky Missouri Ohio Pennsylvania <sup>1</sup> Tennessee Virginia Washington West Virginia <sup>3</sup> Undistributed:	8 13 10 6 58 6 19 18 115	57 10 49 19 7 16 11 10 57 5 22 21 123	12, 923, 860 1, 067, 856 18, 840, 805 5, 103, 522 1, 620, 407 2, 004, 360 1, 236, 799 3, 533, 632 27, 616, 594 314, 54 2, 315, 560 1, 362, 856 23, 384, 440	12, 835, 169 1, 216, 128 22, 126, 723 7, 205, 041 2, 283, 689 3, 005, 717 1, 517, 861 4, 626, 146 229, 948, 020 337, 159 2, 733, 166 1,632, 427 26, 724, 333	84. 3 16. 2 37. 2 27. 0 45. 3 4. 1 39. 9 15. 5 23. 7 5. 2 15. 1 82. 6 18. 5	83. 0 17. 5 40. 4 32. 0 57. 0 5. 6 48. 3 15. 8 23. 0 4. 8 14. 8 88. 7 19. 1
East of Mississippi River 4	3 5	7	64, 785 815, 169	58, 661 1, 219, 617		
Total	6 386	7 416	102, 205, 186	117, 469, 857	22. 2	22. 9

1 Excludes Alaska.

Excludes Alaska.

2 Includes some coal mined in Pennsylvania and cleaned in Ohio.

3 Includes some coal mined in West Virginia and cleaned in Ohio.

4 Includes Georgia and Michigan.

5 Includes Arkansas, Montana, New Mexico, and Utah.

6 Represents 41 plants using both wet and pneumatic methods of cleaning plus 345 plants using only 1 leaving method.

cleaning method.

7 Represents 44 plants using both wet and pneumatic methods of cleaning plus 372 plants using only 1 cleaning niethod.

Table 38.—Result of operations at bituminous-coal-cleaning plants in the United States, by States, in net tons, in 1941 i

Z tulco,	og states, t		10 10 71		
State	Total raw coal moved to cleaning plants 2	Coal ob- tained in cleaning process	Refuse resulting in cleaning process 2	Percent of refuse to raw coal 3	Total production from mines that moved coal to cleaning plants 4
Alabama Colorado Illinois Indiana Kansas Kentucky Missouri Ohio Pennsylvania <sup>5</sup> Tennessee Virginia Washington West Virginia <sup>7</sup> Other States <sup>8</sup>	2, 794, 917 3, 369, 161 1, 917, 673 5, 652, 020 (5) 366, 535 2, 932, 547	12, 835, 169 (9) (22, 126, 723 7, 205, 041 2, 283, 689 3, 005, 717 1, 517, 861 4, 626, 146 (9) 337, 159 2, 733, 166 1, 632, 427 26, 724, 333 23, 190, 883	1, 898, 636 (°) 4, 216, 456 1, 100, 096 511, 228 363, 444 399, 812 1, 025, 874 (°) 29, 376 199, 381 242, 341 3, 111, 209 2, 214, 147	12. 9 9. 6 16. 0 13. 2 18. 3 10. 8 20. 8 18. 2 8. 8 8. 0 6. 8 12. 9 10. 4	13, 822, 090 (9) 34, 786, 567 12, 027, 378 2, 339, 900 6, 517, 713 1, 755, 793 6, 728, 638 (9) 1, 304, 094 9, 699, 108 1, 728, 864 59, 168, 194 35, 520, 165
Total at mines only 9 Consumer plants 10	123, 530, 314 9, 749, 848	108, 218, 314 9, 251, 543	15, 312, 000 498, 305	12. 4 5. 1	185, 398, 504
Grand total	133, 280, 162	117, 469, 857	15, 810, 305	11.9	

<sup>1</sup> Excludes Alaska.

Excludes Alaska.
 Exact figures on raw coal or refuse could not be furnished by many operators; in such instances, estimates were made from all available information at hand.
 In Alabama (for example) for every 100 tons of raw coal cleaned in 1941, an average of 12.9 tons of refuse was discarded and 87.1 tons of clean marketable coal obtained.
 Based upon shipping weights; includes some marketable coal that did not pass through cleaning plants.
 Included with "Other States."
 Includes some coal mined in Pennsylvania and cleaned in Ohio.
 Includes some coal mined in West Virginia and cleaned in Ohio.
 Includes Arkansas, Colorado, Georgia, Michigan, Montana, New Mexico, Pennsylvania, and Utah.
 Includes all mechanical cleaning other than washeries operated by consumer steel companies.
 Includes central washeries in Colorado and Pennsylvania operated by consumer steel companies.

Table 39.—Method of mining at bituminous-coal mines in the United States served by cleaning plants, 1939-41 1

[Does not include any estimate for mines that may ship to consumer-operated plants]

Method of mining in use	Total produc	es that move et tons) 2	Change, 1941 from 1940	
Material of mining in the	1939	1940	1941	(percent)
Mined from strip pits	17, 960, 049 53, 495, 851 61, 805, 096	20, 029, 770 66, 148, 465 75, 493, 332	24, 773, 543 93, 373, 789 67, 251, 172	+23.7 +41.2 -10.9
Total	133, 260, 996	161, 671, 567	185, 398, 504	+14.7

<sup>&</sup>lt;sup>1</sup> Excludes Alaska.
<sup>2</sup> Based upon shipping weights and includes some marketable coal that did not pass through cleaning plants.
DETAILED STATISTICS, BY STATES AND COUNTIES

Detailed production and employment statistics are given in table 40 for each coal-producing county in the United States from which three or more operators submitted reports for 1941. Statistics on counties with less than three reporting producers have been combined with data for other counties in the same State to avoid disclosing individual returns, unless permission to publish has been granted by the operators. Production of mines on the border between two States has been credited to the State from which the coal is extracted rather than that in which the tipple is situated. If the coal is mined from lands in both States, the tonnage has been apportioned accordingly.

In this series the reported production is classified according to the principal methods of distribution or use. Beginning with 1932, the series was expanded to include data on the growing volume of coal moving from mine to consumer by truck. For 1933–36 this tonnage was shown as "commercial sales by truck or wagon." In 1937 this tonnage was shown as "truck deliveries, including local sales." (See Minerals Yearbook, 1939, p. 813.) In 1938 the truck tonnage was shown as "shipped by truck or wagon." The truck figures for 1933 to 1936, inclusive, and 1938 to 1941, inclusive, are reasonably comparable.

The data in this report, like those published for many years by the Bureau of Mines, relate only to mines with an annual output of 1,000 tons or more. Although all mines, regardless of size, are subject to regulation under the provisions of the National Bituminous Coal Act of 1937, it seemed advisable to maintain the continuity of the old series by excluding the very small mines that sell by truck or wagon. This fact should be borne in mind when the statistics in this report are compared with similar data compiled by State mine departments. Differences arise largely from variations in coverage of the State reports, some of which include data for all mines, regardless of size, and others only data for mines employing more than a specified minimum number, which ranges from 2 to 10 men.

Because of a change in the method of reporting, the statistics of average production per man per day for 1932 to 1936 and 1938 to 1941 are not precisely comparable with those for earlier years. Before 1932 they were based upon the calculated number of man-shifts, obtained by multiplying the average number of men employed at each mine by the number of days worked at the mine. Since 1932

operators have been asked to make a special report of the number of man-shifts actually worked, if possible. The number of operators able to furnish this information has been small, although it is increasing from year to year. These reports were utilized to improve the accuracy of the record. Otherwise, the man-shifts were calculated by multiplying the number employed underground and on the surface by the number of days worked by the mine and tipple, respectively.

Table 40.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States in 1941

ī				[E <sub>2</sub>	clusive of mi	nes produci	ng less than	1,000 tons	]					
-			Disposition o	f coal produc	ed (net tons)			Ave	rage numb	er of emplo	yees			
•			Shipped	Used by mine em-	Used at mine for		Average		Sur	face		Average number	Number of	Average
1	County	Loaded for shipment by rail or water 1	by fruck or wagon (excluding coal used by mine employees)	tenders at tipple, or	power and heat or made into beehive coke at mine	Total quantity	value per ton 8	Under- ground	In strip pits	All others	Total	of days mines were active	man-days worked	tons per man per day
_						ALABAM	A		•					
BI Ct	lbb lount ullman towah	677, 489 86, 331 18, 835	16, 028 56, 932 42, 204 13, 604	2,851 533 105	16, 469 1, 632 18	712, 837 145, 428 42, 327 32, 439 33, 473	\$3.01 2.71 2.78 2.72	1, 213 300 106 61	33	200 54 16 13	1,413 387 122 74	199 183 184 188	280, 943 70, 870 22, 456 13, 917	2. 54 2. 05 1. 88 2. 33
Ja Je M	ckson fferson arion leiby uscaloosa	232 8, 125, 625 221, 896 409, 640	33, 241 329, 779 81, 000 110, 567	42, 221 1, 408 2, 919	4 31, 396 196 2, 065	8, 529, 021 304, 500 525, 191	2. 95 2. 71 3. 58 3. 29	12, 190 501 872	6 8	1, 662 1, 662 115 137	75 13, 858 624 1, 009	223 214 204 214	16, 711 2, 972, 394 127, 183 215, 711	2. 00 2. 87 2. 39 2. 43
W O1	instonther counties (Cherokee,	120, 006 3, 392, 845 3, 836	54, 307 173, 527 19, 281	1, 009 <b>53, 424</b> 60	5, 163	175, 322 3, 624, 959 23, 177	2. 38 2. 60 2. 50	311 4, 174 44	94	83 595 7	394 4, 863 51	201 213 162	79, 202 1, 036, 210 8, 283	2, 21 3, 50 2, 80
	Fayette, and St. Clair)	1, 219, 748	33, 898	14, 046	48, 157	1, 315, 849	2. 53	1,740		325	2, 065	262	541,021	2. 43
	Total Alabama	14, 276, 483	964, 368	118, 576	4 105, 096	15, 464, 523	2. 71	21, 572	141	3, 222	24, 935	216	5, 384, 901	2.87
_						ALASK	A							
T	otal Alaska	235, 230			<sup>5</sup> 3, 730	238, 960	\$3.95	110		43	153	311	47, 617	5.02
		•		ARI	ZONA, GEO	RGIA, ID	AHO, ANI	OREGO	ON	<del></del>				
T	otal Arizona, Georgia, Ida- ho, and Oregon	33, 598	19, 468	1,071	8 680	54, 817	\$2.74	136		52	188	222	41, 659	1. 32

Table 40.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States in 1941—Continued

[Exclusive of mines producing less than 1,000 tons]

		Disposition o	f coal produc	ced (net tons)	)		Ave	rage numb	er of emplo	yees			
County	Loaded for shipment by rail or water <sup>1</sup>	Shipped by truck or wagon (excluding coal used by mine employees)	Used by mine employees, taken by locomotive tenders at tipple, or other uses at mine 2	Used at mine for power and heat or made into beehive coke at mine	Total quantity	Average value per ton 3	Under- ground	In strip pits	All others	Total	Average number of days mines were active	Number of man-days worked	Average tons per man per day
					ARKAN	SAS						•	
Franklin Johnson Logan Sebastian Other counties (Pope and	65, 668 237, 578 458, 319 705, 973	9, 128 16, 464 3, 749 31, 552	399 781 2, 098 782	1, 923 1, 856 1, 928 1, 375	77, 118 256, 679 466, 094 739, 682	\$3. 54 3. 40 4. 52 3. 35	224 481 1, 179 1, 174	22 17 81	35 111 213 215	281 609 1, 392 1, 470	100 137 131 153	28, 084 83, 737 182, 583 225, 479	2. 75 3. 07 2. 55 3. 28
Scott) Total Arkansas	31, 511 1, 499, 049	1, 722 62, 615	4, 180	1, 246 5 8, 328	34, 599 1, 574, 172	3.74	3, 267	120	601	3, 988	134	14, 908 534, 791	2.32
			<u> </u>	<u> </u>	COLORA	D0	<u>.</u>				<u> </u>		<u> </u>
Boulder Delta El Paso Fremont Garfield Gunnison Huerfano La Plata Las Animas Mosa Moffat Montrose Rio Blanco Routt Weld	12, 569 1, 153, 863 65, 099 27, 109	418, 534 28, 015 160, 383 350, 053 28, 422 19, 879 70, 193 18, 614 54, 153 36, 125 13, 485 37, 171 12, 235 19, 792 324, 525	6, 484 423 37, 405 3, 564 50 8, 607 3, 918 230 6, 286 568 8, 865 7, 808 134 14, 537 10, 972	6, 062 4, 201 6, 882 2, 704 1, 225 10, 711 1, 789 30 6 137, 817 4, 462	654, 334 73, 244 237, 552 516, 161 37, 344 708, 037 815, 632 31, 443 1, 352, 119 106, 254 49, 459 44, 979 12, 379 878, 952 1, 276, 231	\$2. 90 2. 76 2. 89 3. 12 3. 11 2. 62 2. 91 2. 32 2. 96 2. 41 2. 94 2. 72 3. 22 3. 22 3. 23 2. 32 3. 23 3. 23 23 23 23 23 23 23 23 23 23 23 23 23 2	574 55 166 631 32 487 821 31 1, 457 96 17 46 14 868 929	1	116 22 39 132 12 135 173 7 219 19 3 6 3 263 202	691 77 205 763 44 622 994 38 1, 676 115 30 52 17 1, 131	244 215 232 196 246 227 201 241 230 214 221 307 242 165 214	168, 843 16, 523 47, 483 149, 407 10, 809 141, 320 199, 882 9, 155 384, 676 24, 641 6, 644 15, 971 4, 120 187, 179 241, 783	3. 88 4. 43 5. 00 3. 45 5. 01 4. 08 3. 43 3. 51 4. 31 7. 4. 31 7. 2. 82 3. 00 4. 70 5. 28

Other counties: Elbert, Jackson, Jefferson, and Larimer Montezuma and Pitkin Total Colorado	101, 877 60 4, 958, 827	44, 591 4, 644 1, 640, 814	1, 127 1, 212 112, 190	901 6 236, 701	148, 496 5, 916 6, 948, 532	2. 46 3. 30 2. 83	112 9 6,345	15 16	25 3 1,389	152 12 7,750	237 214 213	36, 017 2, 562 1, 647, 015	4. 12 2. 31 4. 22
ILLINOIS													
Bureau. Christian Clinton Edgar Franklin Fulton Gallatin Grundy Henry Jackson Knox LaSalle Livingston Macoupin Madison Menere Peoria Perry Randolph Rock Island St. Clair Saline Sangamon Schuyler Shelby Stark Vermilion Washington Washington	1, 290 498, 676 1, 887, 676 598, 821 102, 422 3, 903, 822 933, 230 330, 923 3, 763, 036 1, 438, 439 1, 438, 439 4, 637, 048 2, 043, 442 23, 952	56, 039 123, 946 88, 846 26, 533 96, 541 448, 541 839, 306 78, 465 114, 916 86, 300 193, 142 291, 312 297, 532 824, 895 120, 516 17, 737 474, 533 80, 029 85, 992 15, 604 1, 190, 402 1, 462 268, 546 78, 777 8, 154 9, 837 429, 886 683, 244 693, 459	2, 348 1, 350 2, 870 92 88, 252 7, 570 1, 101 1, 278 3, 898 1, 977 14, 928 24, 818 14, 214 2, 160 270 1, 657 6, 803 4, 484 4, 484 15 137, 754 11, 172 900 4, 381 12, 190 3, 300 4, 381 15, 852	3, 586 16, 688 13, 103 2, 383 160, 299 12, 702 2, 863 1, 709 6, 647 2, 845 2, 845 2, 845 120 137, 429 70, 807 1, 753 50 1, 536 39, 774 26, 719 43, 155 47, 563 21, 629 1, 115 41, 115 41, 115 42, 636 36 61, 015 11, 149 49, 636 85, 027	62, 739 5, 557, 014 229, 530 10, 211, 626 4, 833, 673 43, 464 81, 275 615, 464 1, 984, 445 4, 903, 601 1, 443, 146 1, 843, 146 4, 803, 601 1, 443, 146 3, 889, 642 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 565, 614 1, 566, 920 2, 644, 789 1, 566, 920 2, 644, 789 1, 566, 920 2, 647, 746 2, 955, 254	\$3. 26 1. 52 1. 70 2. 13 1. 90 1. 90 1. 90 2. 02 1. 79 2. 08 2. 97 2. 97 2. 97 2. 23 3. 20 2. 20 6. 1. 63 1. 63 1. 74 2. 07 1. 83 8. 11 1. 74 2. 07 1. 88 1. 87 2. 67 2. 67 2. 67 2. 67 2. 67	213 1,706 278 51 4,780 629 627 75 178 647 258 419 258 419 1,362 2,187 1,249 1,352 2,187 67 67 75 31 1,352 2,187 1,352 2,187 1,352 2,187 1,352 2,187 1,352 2,187 1,352 2,187 1,352 2,187 1,352 1,352 1,352 1,352 1,352 1,352 1,352 1,231	3857 78 89 61 64 3 3 389 51 107 155 111 37	16 530 47 9 1, 445 482 211 101 107 100 80 5 464 222 5 316 210 334 222 58 334 222 58 33 330 512	229 2, 236 326 6, 225 1, 468 88 107 357 933 419 563 33 2, 651 1, 578 40 934 1, 775 2, 781 106 37 2, 204 283 1, 614 2, 050	132 214 139 140 170 227 134 178 208 223 203 203 203 204 216 197 184 200 184 166 144 182 178 217 209 220 223 218 219 210 216 217 218 217 218 217 218 217 218 217 218 217 218 217 218 217 218 217 218 218 218 218 218 218 218 218 218 218	30, 292 478, 806 45, 880 8, 412 1, 057, 473 333, 733 11, 835 19, 128 74, 167 208, 466 93, 275 114, 461 3, 848 565, 452 314, 268 38, 394 7, 868 317, 336 112, 763 117, 336 112, 763 254, 821 496, 416 495, 032 22, 969 7, 739 4, 840 363, 884 38, 571 292, 159 356, 914	2. 07 11. 61 5. 09. 66 14. 48 3. 67 4. 27 8. 30 9. 52 8. 35 8. 21 15. 86 13. 80 2. 29 71 12. 26 13. 80 5. 34 4. 56 1. 06 5. 34 4. 56 1. 06 5. 34 6. 20 7. 80 7. 80
Total Illinois	46, 246, 919	7, 314, 004	370, 449	\$ 771, 912	54, 703, 284	1.81	25, 396	1, 751	6, 920	34, 067	186	6, 343, 392	8 8. 62

Table 40.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States in 1941—Continued

[Exclusive of mines producing less than 1,000 tons]

		Disposition o	f coal produc	ced (net tons	)		Ave	erage numb	er of emplo	yees			
County	Loaded for	Shipped by truck	Used by mine em- ployees,	Used at mine for		Average value		Sur	face		Average number of days	Number of	Average tons per
·	shipment by rail or water 1	or wagon (excluding coal used by mine employees)	taken by locomotive tenders at tipple, or other uses at mine 2	power and heat or made into beehive coke at mine	Total quantity	per ton 3	Under- ground	In strip pits	All others	Total	mines were active	man-days worked	man per day
				Annual Commence	INDIA	<b>VA</b>							
Olay Daviess Dubois Fountain Gibson Greene Knox	1, 505, 404 	499, 213 81, 818 13, 839 73, 921 139, 745 84, 849 370, 373	2,852 478 32 85 2,335 6,201	6, 241 843 67 489 24, 847 12, 847 18, 216	2, 013, 710 83, 139 13, 906 85, 844 1, 157, 862 2, 591, 754 2, 863, 350	\$1. 98 2. 32 2. 19 2. 33 1. 79 1. 76 1. 56	111 50 12 22 482 334 1,054	460 9 4 34 275 19	337 19 5 16 103 509 345	908 78 21 72 585 1, 118 1, 418	191 226 193 143 177 210 240	173, 745 17, 630 4, 062 10, 318 103, 636 234, 270 340, 885	11. 59 4. 72 3. 42 8. 32 11. 17 11. 06 8. 41
Parke. Perry Pike Spencer Sullivan Vermillion Vigo		115, 917 40, 837 68, 317 32, 043 103, 466 114, 365 259, 840 196, 760	0, 200 270 178 15, 968 387 3, 678 582 344, 633 2, 737	18, 210 2, 770 39 13, 389 117 20, 712 2, 290 19, 376 4, 545	2, 803, 830 118, 957 41, 054 4, 253, 896 144, 940 2, 059, 467 519, 039 3, 751, 630 2, 611, 389	2. 65 1. 87 1. 47 2. 42 1. 93 1. 80 1. 71 1. 51	1,039 179 57 36 34 773 323 1,333 273	483 33 139 76 166 170	35 6 496 34 327 124 457 342	1, 416 63 1, 015 101 1, 239 523 1, 956	183 222 208 192 187 144 189	39,072 13,986 210,861 19,362 231,894 75,179 369,802 179,652	3. 04 2. 94 20. 17 7. 49 8. 88 6. 90 10. 14 14. 54
Other counties (Martin, Owen, Vanderburgh, and Warren)	105, 667	62, 790	315	220	168, 992	2.03	113	17	39	169	155	26, 259	6. 44
Total Indiana	19, 718, 097	2, 258, 093	380, 731	<sup>8</sup> 127, 008	22, 483, 929	1.70	5, 186	1,885	3, 194	10, 265	200	2, 050, 613	8 10. 96
	<u> </u>				IOWA								
AdamsAppanooseBooneGreene	200, 823 164, 867 260	22, 759 181, 549 65, 566 16, 574	57 3, 666 5, 632 117	46 920 1,805 10	22, 862 386, 958 237, 870 16, 961	\$3, 50 2, 77 3, 33 3, 32	108 1, 183 475 35	5	17 140 43 8	125 1,323 518 48	158 127 184 113	19, 808 167, 494 95, 539 5, 406	1. 15 2. 31 2. 49 3. 14

四	
U	
BITUMINOUS	
3	
ğ	
COAL	
F	
AND	
Ð	
E	
8	
FIGUITE	
円	

Guthrie Jasper Lucas Mahaska Marion Monroe Page Polk Van Buren Wapello Warren Wayne Webster Cother counties (Dallas, Davis, Jefferson, Keokuk, and Taylor)	36, 789 2, 973 16, 220 213, 472	21, 656 50, 934 22, 833 137, 920 386, 210 88, 309 39, 233 224, 420 117, 402 55, 118 18, 297 20, 605 99, 986 1, 593, 009	467 721 2, 122 1, 144 3, 898 2, 385 11, 748 200 632 986 250 223 5, 002	24 130 901 1, 138 3, 307 2, 195 1, 651 145 730 1, 890 1, 212	22, 137 52, 627 130, 528 150, 4713 183, 850 39, 233 318, 765 156, 553 60, 967 18, 647 37, 048 319, 672 2, 938, 626	4. 02 2. 88 2. 65 2. 44 2. 38 2. 27 3. 78 2. 96 2. 91 2. 58 3. 16 2. 75 3. 10 2. 75 3. 10	74 68 238 47 446 281 86 630 17 175 80 56 65 66 36	14 96 139 6 7 15 22 15 4 8 331	9 17 28 72 108 45 9 70 34 9 13	83 99 286 215 693 332 95 682 41 287 129 53 559	159 166 120 190 187 159 236 152 171 145 112 173 236	13, 162 16, 448 31, 831 40, 850 129, 633 52, 807 22, 458 103, 344 6, 993 38, 641 11, 223 12, 485 99, 775	1. 68 3. 20 4. 11 7. 72 4. 59 3. 48 1. 75 3. 08 3. 54 4. 03 4. 22 1. 66 2. 97 3. 20
					KANSA	s							
Bourbon Cherokee Crawford Labette Linn Osage Other counties (Franklin and Leavenworth) Total Kansas 9	153, 249 964, 162 1, 731, 043 	14, 962 56, 861 129, 186 15, 548 23, 245 89, 356 14, 589	316 1, 619 9, 799	1, 092 1, 868 5, 958 720 460	169, 351 1, 025, 975 1, 870, 919 16, 268 759, 244 92, 805 73, 010 4, 007, 572	\$2.00 2.07 2.06 2.58 1.56 3.44 2.18	47 870 46 269 282 1,514	44 128 284 15 50 4	20 204 279 6 84 32 98	64 379 1, 433 21 180 305 380 2, 762	221 201 191 163 220 158 264	14, 156 76, 109 273, 906 3, 428 39, 610 48, 197 100, 425 555, 831	11. 96 13. 48 6. 83 4. 75 19. 17 1. 93 . 73
Eastern district:  Bell	8, 994 36, 559 224, 521 5, 472, 029 14, 087, 519 723, 923 413, 938 522, 562	133, 890 71, 344 4, 650 82, 527 89, 372 7, 073 5, 036 30, 578 261, 051 2, 704 3, 101 35, 464	17, 072 114 44, 870 2, 473 2, 202 10, 544 20 76, 928 76, 928 117 4, 801 2, 032 5, 511	3, 938 25 18, 554 10, 400 11 7, 851 1, 297	2, 618, 856 71, 458 58, 514 121, 559 316, 120 5, 508, 200 6, 505 14, 205, 425 269, 019 732, 725 419, 071 564, 362	\$2. 35 2. 25 2. 25 2. 16 2. 19 2. 32 2. 03 2. 43 2. 32 2. 65 2. 24 2. 31	3, 115 174 115 165 560 4, 697 13 14, 146 432 885 419 822		468 37 19 54 138 737 3 1,718 88 115 58	3, 583 211 134 219 698 5, 434 16 15, 864 520 1, 000 477 949	207 250 162 237 222 210 148 227 246 236 185	740, 427 52, 832 21, 678 51, 803 154, 820 1, 140, 772 2, 370 3, 603, 769 235, 519 88, 323 184, 568	3. 54 1. 35 2. 70 2. 35 2. 04 4. 83 2. 13 2. 10 3. 11 4. 74 3. 06

Table 40.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States in 1941—Continued

[Exclusive of mines producing less than 1,000 tons]

		Disposition o	of coal produc	ced (net tons	)		Ave	rage numb	er of emplo	yees			
		Shipped	Used by mine em-	Used at mine for		Average		Sur	face		Average number	Number of	Average
County	Loaded for shipment by rail or water 1	by fruck or wagon (excluding coal used by mine employees)	ployees, taken by locomotive tenders at tipple, or other uses at mine?	power and heat or made into beehive coke at mine	Total quantity	value per ton 3	Under- ground	In strip pits	All others	Total	of days mines were active	man-days worked	tons per man per day
				KEI	NTUCKY—	Continued							
Eastern district—Continued. Laurel. Lawrence. Lee. Letcher. Martin. Menifee. Perry. Pike. Pulaski. Rockcastle. Whitley. Wolfe. Other counties 12.	373	70, 780 7, 905 19, 256 5, 250 1, 250 5, 538 11, 995 52, 467 54, 113 14, 536 13, 861 17, 661	25 76 65 22, 390 86 121, 086 208, 116 44 2, 073 55 12, 931 533, 630	451 100 5 6, 237 109 2, 329 25 8, 677 5	94, 543 10, 080 27, 071 4, 586, 438 318, 561 1, 538 5, 446, 301 5, 383, 545 54, 113 15, 040 390, 961 13, 921 914, 965	\$2. 26 3. 45 2. 22 2. 33 1. 97 2. 26 2. 32 2. 08 2. 11 2. 11 2. 64 4. 194 2. 39	192 21 45 4,448 192 14 4,707 4,508 101 23 754 20 1,188	14	50 8 10 525 38 4 721 877 36 15 132 6 205	255 29 55 4,973 230 18 5,428 5,385 137 38 900 26 1,393	218 248 222 209 206 206 208 209 176 234 177 238 217	55, 665 7, 205 12, 230 1, 038, 055 47, 442 3, 710 1, 128, 705 1, 126, 263 2, 4, 080 8, 890 159, 303 6, 200 301, 956	1. 70 1. 40 2. 21 4. 42 6. 71 1. 49 4. 83 4. 75 2. 25 5. 1. 69 2. 51 2. 25 3. 03
Western district: Butler	904 44, 816 9, 035 11, 282 5, 020, 154 3, 508, 835 119, 280 676, 419	37, 839 19, 874 138, 793 23, 817 106, 732 266, 711 210, 950 54, 592 113, 237 25, 478	15 439 614 114 840 45,738 5,878 1,339 31,466 80	36 1, 486 3, 281 6, 237 7, 620 55, 211 75 12, 858 6, 757	38, 794 66, 615 151, 723 23, 931 125, 091 5, 340, 223 3, 780, 874 175, 286 833, 980 1, 031, 561	1. 68 1. 76 1. 45 1. 69 1. 67 1. 59 1. 56 1. 41 1. 55 1. 54	69 68 139 42 214 2, 456 2, 285 186 661 883	18	21 17 43 9 46 683 530 48 117	90 103 182 51 260 3, 253 2, 815 234 778 1, 025	192 160 198 201 164 219 216 211 220 215	17, 309 16, 510 35, 983 10, 269 42, 542 710, 830 609, 124 49, 476 171, 460 220, 837	2. 24 4. 03 4. 22 2. 33 2. 94 8 7. 51 6. 21 3. 54 4. 86 4. 67

BIT	
NOUS	
COA	
Ā	
S	
E	
3	
H	

Total Kentucky 50, 882, 955 2, 052, 833 620, 169 11 154, 389 53, 710, 346 2. 17 48, 789 159 7, 857 56, 796 215 12, 213, 755 4. 4  MARYLAND  MARYLAND  Allegany. 812, 912 181, 955 10, 262 805 1, 005, 934 82. 51 1, 271 1 151 1, 422 217 309, 055 3.2  Garrett. 614, 297 70, 140 3, 622 805 1, 700, 594 2. 40 1, 957 8 266 8 115 809 213 172, 113 4. 0  Total Maryland 1, 427, 200 252, 065 13, 884 7, 886 1, 700, 574 2. 40 1, 957 8 266 2, 231 216 481, 198 3.5  MICHIGAN  Saginaw	Other counties (Edmonson and McLean)		11,810	16		11, 826	1. 63	21		12	33	147	4, 840	2. 44
MARYLAND	Total Western Kentucky.	10, 389, 971	1, 009, 833	86, 539	93, 561	11, 579, 904	1. 57	7,024	132	1, 668	8, 824	214	1, 889, 180	6. 13
Allegany	Total Kentucky	50, 882, 955	2, 052, 833	620, 169	11 154, 389	53, 710, 346	2. 17	48, 780	159	7, 857	56, 796	215	12, 213, 755	4. 40
Carrett   Carr		-				MARYLA	ND							
Sagfnaw	AlleganyGarrett	812, 912 614, 297		10, 262 3, 622		1, 005, 934 694, 640	\$2. 51 2. 26	1, 271 686	8		1, 422 809	217 213		3. 25 4. 04
Saginaw	Total Maryland	1, 427, 209	252, 095	13, 884	5 7, 386	1, 700, 574	2.40	1, 957	8	266	2, 231	216	481, 198	3. 53
Cher counties (Bay, Huron, Shiawassee, and Tuscola). 112,879 127,007 5,619 8,437 253,942 4.17 513	And the second s			<u>'</u>		MICHIG	AN		<u> </u>	<u>'</u>				
Shiawassee, and Tuscola)	Saginaw	6, 766	46, 161	1, 146	2, 760	56, 833	\$4.48	159		28	187	165	30, 816	1.84
Adair	Shiawassee, and Tuscola)	112, 879	127, 007	5, 619	8, 437	253, 942	4. 17	513		57	570	161	91, 803	2.77
Adair	Total Michigan	119, 645	173, 168	6, 765	<sup>6</sup> 11, 197	310, 775	4. 22	672		85	757	162	122, 619	2, 53
Batton         202, 042         24, 654         338         1,300         228, 424         2.15         8         61         33         102         172         17,559         10 13,05           Bates         85,177         33,350         225         3,047         121,799         2.06         19         65         12         96         172         16,535         10 7,3           Boone         22,149         26         14         22,189         2.31         23         18         7         48         156         7,476         2.9           Callaway         161,361         300         415         162,076         2.14         13         48         16         77         259         19,923         10 8.1           Clay         114,457         2,758         2,272         149,487         3.15         444         42         486         164         77         469         49,962         1.8           Harrison         23,088         150         459         23,697         3.04         60         9         69         163         11,281         2.1           Henry         464,750         127,239         237         4,460         596,686			'		· · · · · · · · · · · · · · · · · · ·	MISSOU	RI							
	Barton Bates Boone Callaway Clay Harrison Henry Lafayette Linn Macon Putnam Ralls Randolph Ray Vernon Other counties <sup>18</sup>	202, 042 85, 177 464, 750 111, 697 12, 807 369, 890 900 459, 701 15, 783 30, 638 9, 479	24, 654 33, 350 22, 149 161, 361 144, 457 23, 088 127, 239 111, 792 62, 285 65, 564 54, 823 14, 276 112, 181 143, 268 38, 685 70, 974	338 225 26 300 2,758 150 237 4,095 1,284 3,136 182 89 902 4,009 254 60	1, 390 3, 047 14 415 2, 272 459 4, 460 2, 077 70 1, 785 44 	228, 424 121, 799 22, 189 162, 076 149, 487 23, 697 596, 686 229, 661 76, 426 440, 375 55, 049 15, 265 572, 794 163, 842 71, 897 82, 275	2. 15 2. 06 2. 31 2. 14 3. 15 3. 04 1. 94 2. 83 2. 75 1. 85 2. 28 2. 55 2. 28 3. 10 2. 08 2. 67	8 19 23 13 444 60 47 680 195 117 159 32 180 590 20 86	65 18 48 201 63 6 40 51 100	33 12 7 16 42 9 120 69 15 75 38 6 90 51 17 42	102 96 48 77 486 69 368 749 210 255 197 44 310 641 88 228	172 172 156 259 164 163 170 154 210 191 140 187 237 136 132	17, 559 16, 585 7, 476 19, 923 79, 462 11, 281 62, 559 115, 589 44, 047 48, 608 27, 500 8, 230 73, 371 87, 062 211, 626 34, 426	3. 18 10 13. 01 10 7. 37 2. 97 10 8. 14 1. 88 2. 10 10 9. 54 1. 99 1. 74 10 9. 06 2. 00 1. 85 10 7. 81 1. 88 10 6. 18 2. 39
Total Missouri •	Total Missouri	1, 797, 266	1, 304, 795	18, 365	5 24, 862	3, 145, 288	2. 23	2, 856	653	679	4, 188	169	707, 194	4. 45

Table 40.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States in 1941—Continued

[Exclusive of mines producing less than 1,000 tons]

	1					1		<u>-</u>			i i	1	
		Disposition o	of coal produc	ced (net tons	)		A	verage num	ber of emp	loyees			
County		Shipped by truck	Used by mine em-	Used at mine for		Average		Sur	face		Average number	Number of	Average
County	Loaded for shipment by rail or water !	or wagon (excluding coal used by mine employees)	ployees, taken by locomotive tenders at tipple, or other uses at mine 2	power and heat or made into beehive coke at mine	Total quantity	value per ton 3	Under- ground	In strip pits	All others	Total	of days mines were active	man-days worked	tons per man per day
					MONT	INA					•		
Montana bituminous coal: Carbon	31 791 757	33, 560 31, 608 5, 804 7, 221 45, 150	3, 036 1, 168 50 90 3, 585	497 129 3, 274	411, 088 506, 261 5, 854 7, 342 843, 766	\$2. 10 1. 47 3. 76 3. 70 2. 01	151 249 9 10 420		103 39 2 3 179	254 288 11 13 599	198 209 153 218 182	50, 205 60, 098 1, 678 2, 837 109, 268	8. 19 8. 42 3. 49 2. 59 7. 72
Rosebud_ Other counties 14	1, 395, 008	3, 399 20, 836	943 128	306	1, 399, 350 21, 270	. 92 4. 05	6 41	47	14 10	67 51	272 206	18, 240 10, 491	10 76. 72 2. 03
Total bituminous coal Montana lignite	3, 034, 147 4, 483	147, 578 54, 042	9,000 228	4, 206 40	3, 194, 931 58, 793	1. 48 1. 79	886 68	47 8	350 22	1, 283 98	197 174	252, 817 17, 083	12. 64 3. 44
Total Montana	3, 038, 630	201, 620	9, 228	<sup>5</sup> 4, 246	3, 253, 724	1.48	954	55	372	1, 381	195	269, 900	12.06
					NEW ME	XICO							
Colfax	1	26, 194 70, 481 4, 746 4, 841 4, 948	3, 043 4, 676 	3,062 31,514	562, 781 520, 291 32, 688 4, 841 4, 972	\$2. 88 3. 21 2. 10 3. 60 1. 73	463 656 54 17 14		117 205 13 4 4	580 861 67 21 18	184 223 241 114 167	106, 709 192, 413 16, 174 2, 400 3, 010	5. 27 2. 70 2. 02 2. 02 2. 02 1. 65
Socorro)	95,048	21, 980	3, 437	5, 082	125, 547	3. 22	223		53	276	285	78, 756	1, 59
Total New Mexico	1,067,092	133, 190	11, 180	* 39, 658	1, 251, 120	3.03	1, 427		396	1,828	219	399, 462	3. 13

### NORTH DAKOTA (LIGNITE)

tal North Dakota	1, 709, 100	411, 880	18 163, 515	5 24, 393	2, 308, 888	\$1. 27	562	444	269	1, 275	177	225, 657	10. 2
					оні	)							
hens	1, 976, 974	70, 542	3, 203	17, 566	2, 068, 285	\$2. 12	1, 669		440	2, 109	201	424, 321	4. 8
lmont	7, 980, 827	184, 026	27, 872	19, 167	8, 211, 892	1.96	5, 615	42	867	6, 524	233	1, 517, 367	5. 4
rroll	196, 646 60, 613	473, 449 953, 466	2, 125 955	737	672, 957	2. 15 2. 06	361 272	89	105	555	225 220	124, 883	5.
lumbianashocton	29, 620	305, 701	680	547 1, 288	1, 015, 581 337, 289	2.00	293	159 16	122 57	553 366	220	121, 767	10 8.
llia	8, 892	88, 182	34	1, 288	97, 208	2. 18	293 93	12	23	128	191	79, 514 24, 469	4. 3.
ernsey	517, 108	78, 351	2, 238	100	597, 697	1.95	504	12	53	557	225	125, 555	3. 4.
arrison	3, 782, 420	37, 971	436	11, 410	3, 832, 237	1. 84	1, 147	214	399	1,760	240	422, 824	8 9
ocking	234, 669	155, 578	1,004	11,410	391, 256	2. 12	380	8	52	440	202	88, 835	4.
cking lmes	201,000	47, 297	22	33	47, 352	2. 50	43	4	10	57	209	11, 921	3
kson	65, 830	93, 221	22, 566	6	181, 623	2. 23	207	22	34	263	210	55, 317	3
ferson	5, 430, 966	407, 361	9, 135	14, 973	5, 862, 435	1.98	2, 815	326	778	3, 919	234	916, 518	8 6
wrence		112, 253	7, 838	22,00	120, 096	2.01	141	020	778 21	162	236	38, 302	3
honing		409, 635	753	2, 591	412, 979	2. 32	41	97	33	171	247	42, 154	10 9
igs	111,055	139, 665	82	_,	250, 802	1. 91	247		34	281	226	63, 375	3
organ	187, 489	8,492			195, 981	2.11	159		27	186	260	48, 401	4
ıskingum	959, 980	299, 367	222	207	1, 259, 776	1.84	660	17	111	788	212	167, 246	8 7
ту	694, 977	300. 914	2, 327	579	998, 797	1.98	1,002	49	185	1, 236	177	218, 255	4
rk	794	911, 448	412	84	912, 738	2.00	130	265	112	507	207	104, 808	10 8
iscarawas	86, 179	1, 509, 184	961	316	1, 596, 640	2. 19	833	270	226	1, 329	211	279, 936	- 5
nton	4, 259	136, 430	36	2, 305	143, 030	2. 18	65	74	25	164	227	37, 270	3
ashington		6,755			6, 755	2.47	13		3	16	181	2,896	2
ayne		24, 721			24, 721	2.46	21	6	6	33	124	4, 089	10 6
her counties (Noble, Port-			F00	- 000	00 ==0							11.71.12	
age, and Trumbull)		79, 156	500	1,060	80, 716	2. 55	23	15	18	56	299	16, 763	4
Total Ohio	22, 329, 298	6, 833, 165	83, 401	§ 72, 979	29, 318, 843	1. 99	16, 734	1,685	3, 741	22, 160	223	4, 936, 786	5
					OKLAHO	MA							
al		21, 766	133	19	21, 918	\$4.02	43	2	14	59	167	9, 871	2.
aig		13, 512	30	101	13, 643	2.83		23		23	168	3, 864	3.
timer	32, 880	1,641	7	109	34, 637	3. 69	58		13	71	198	14,090	2
Flore	366, 857	3, 551	400	2,011	372, 819	3. 34	685		145	830	147	122, 118	3
mulgee	330, 867	36, 424 27, 706	108	690	368, 089	2. 35	327		56	383	176	67, 394	8 5
tsburg	130, 866 76, 521	27, 706 26, 709	1, 619	1,736	161, 927	3.69	283		73	356	167	59, 480	. 2
gers lsa	6, 530	26, 709 28, 778	50	2, 957 30	106, 187 35, 388	2. 43 2. 90	2 82	54	19	75	272	20, 382	10 5
her counties:	0,000	20,118	ĐU	30	30, 388	2.90	82		13	95	158	14, 992	2
Haskell and Sequoyah	100, 441	2,903	165	868	104, 377	2. 67	44	39	27	110	213	00 400	
Muskogee and Wagoner	527, 225	24, 381	517	800	552, 123	1. 99	16	65	55	136	213	23, 483	10 10
The state of the s		21,001	011		002, 120	1. 00	10	00	00	190	444	30, 167	10 18
	1 1			8, 521	1,771,108	2. 65	1, 540						
Total Oklahoma	1, 572, 187	187, 371	3, 029	I G X. DZI	1.771.108.1	2 00 1	1.540	183	415	2, 138	171	365, 841	4.

Table 40.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States in 1941—Continued

[Exclusive of mines producing less than 1,000 tons]

					<b>F</b>	-6 -000	,000	4					•
		Disposition o	of coal produ	ced (net tons	)		Ave	rage numb	er of emplo	yees			
		Shipped	Used by mine em-	Used at mine for				Sur	face		Average		Average
County	Loaded for shipment by rail or water 1	by fruck or wagon (excluding coal used by mine employees)	ployees, taken by locomotive tenders at tipple, or other uses at mine <sup>2</sup>	power and heat or made into beehive coke at mine	Total quantity	Average value per ton 3	Under- ground	In strip pits	All others	Total	of days mines were active	Number of man-days worked	tons per man per day
			P	ENNSYLV	ANIA (BIT	UMINOU	S COAL)						
Allegheny Armstrong Beaver Bedford Blair Bradford Butler Cambria Center Clarion Clearfield Clinton Elk Frayette Greene Huntingdon Indiana Jefferson Lawrence Lycoming Mercer Somerset Tioga Venango Washington Westmoreland Other counties (Cameron, Forest, Fulton, and McKean)	611, 414 16, 090, 373 719, 765 1, 813, 275 4, 166, 513 54, 047 699, 094 16, 677, 510 6, 035, 255 411, 888 7, 442, 940 2, 147, 360 192, 489 2, 000	2, 298, 521 200, 341 665, 679 115, 809 116, 600 10, 185 537, 213 525, 625 225, 993 337, 130 463, 418 65, 510 115, 139 1, 617, 568 59, 079 94, 659 175, 632 116, 861 63, 403 332, 743 199, 083 96, 065 25, 453 676, 525 1, 251, 799	1, 081, 928 47, 344 8, 772 212, 184 1, 228 10, 848 1, 721, 834 5, 932 5, 391 165 4, 429 102, 608 13, 908 13, 908 3, 483 305, 717 3, 199 172 250 1, 457 30, 375 348 10 284, 558 196, 527	12, 118 593 6, 069 616	16, 135, 666 5, 067, 762 980, 542 470, 324 10, 197 1, 159, 940 18, 602, 829 961, 98 2, 185, 632 4, 658, 378 389, 591 22, 793, 166 6, 132, 243 512, 975 8, 315, 015 2, 329, 686 309, 649 65, 783 448, 146 6, 314, 140 339, 745 25, 463 20, 097, 652 10, 930, 010	\$2. 20 2. 15 2. 14 2. 65 3. 19 2. 27 2. 48 2. 16 2. 04 2. 26 2. 22 2. 26 2. 34 2. 19 2. 66 2. 11 2. 19 2. 42 2. 58 2. 26 2. 43 2. 90 2. 47 2. 25 2. 18	11, 422 4, 045 200 652 298 14 1, 038 17, 831 91 1, 283 4, 534 74 952 18, 324 4, 340 759 6, 374 2, 131 340 98 212 6, 076 313 32 5, 076 315 315 82 7, 506	206 150 181 	1, 748 92 94 30 2 174 2, 714 139 255 712 2, 194 162 2, 194 700 78 78 16 66 882 55 6 2, 014 1, 204	13, 376 4, 748 473 746 328 16 1, 308 20, 568 1, 226 5, 530 1, 1826 5, 530 1, 104 20, 764 11, 7 320 398 344 18, 130 9, 060	224 214 243 197 216 250 208 223 203 211 216 224 227 228 224 212 201 226 241 221 199 255 225 234	2, 994, 908 1, 018, 300 1, 14, 866 146, 742 70, 765 4, 004 272, 137 4, 581, 680 248, 911 386, 008 1, 194, 676 27, 968 250, 364 4, 728, 611 1, 152, 879 188, 740 1, 606, 769 1, 544, 148 7, 132 26, 401 76, 996 1, 544, 148 7, 132 26, 401 76, 996 1, 544, 148 78, 132 26, 401 77, 913 78, 137 79, 137	5. 39 4. 97 8 8. 54 3. 21 2. 76 2. 55 4. 26 4. 06 3. 80 4. 28 3. 35 4. 82 2. 72 5. 32 2. 72 4. 37 3. 55 82 4. 29 2. 94 5. 15
			4 077 719									67, 761	3. 66
Total Pennsylvania	109, 081, 289	10, 562, 884	4, 077, 713	16 6, 517, 797	130, 239, 683	2. 28	105, 899	2, 514	15, 075	123, 488	224	27, 605, 388	4. 72

Total South Dakota	37, 338	33, 364	15 123	(18)	70, 825	\$1.52	15	44	10	69	174	12, 001	5. 90
·					TENNES	SEE							
Anderson. Campbell Claiborne Fentress Grundy Hamilton Marion Morgan Overton Scott. Sequatchie White Other counties:	1, 170, 595 1, 894, 216 1, 711, 258 349, 296 454, 203 20, 484 405, 281 133, 272 15, 710 119, 151 18, 575	30, 884 60, 203 38, 079 23, 514 6, 157 30, 756 85, 191 15, 431 28, 253 16, 464 89, 728 5, 670	8, 994 27, 833 14, 990 2, 121 6, 603 125 4, 204 1, 518 11 1, 732 290	423 193 4, 098 6, 532 17 12, 764 1, 541 10, 075 180 2, 406 582	1, 210, 896 1, 982, 445 1, 768, 425 381, 463 479, 727 51, 365 496, 217 160, 296 44, 154 139, 753 109, 175 5, 670	\$2. 38 2. 52 2. 25 1. 86 2. 34 2. 04 2. 61 2. 06 1. 61 2. 23 2. 15 1. 77	1, 310 2, 174 1, 784 354 493 71 731 293 41 240 144 13	3	139 362 268 41 62 17 115 81 8 44 32	1, 449 2, 536 2, 052 395 555 88 846 374 49 287 176	214 225 226 256 212 198 206 168 250 176 19	309, 962 571, 214 463, 421 100, 930 117, 925 17, 431 174, 334 62, 776 12, 248 50, 622 35, 019 3, 136	3. 91 3. 47 3. 82 3. 78 4. 07 2. 95 2. 85 2. 55 3. 60 3. 12 1. 81
Cumberland and Putnam	85, 723	42, 276	837	66	128, 902	1.81	157		52	209	238	49, 805	2. 59
Bledsoe, Rhea, and Van Buren	34, 065	52, 649	69		86, 783	2.11	121		21	142	202	28, 734	3. 02
Total Tennessee	6, 411, 829	525, 255	69, 327	17 38, 860	7, 045, 271	2.34	7, 926	3	1, 243	9, 172	218	1, 997, 557	3. 53
					TEXA	3							
Texas bituminous coal: Palo Pinto and Wise	10, 074	5, 282	126		15, 482	\$3.41	57		11	68	94	6, 405	2. 42
Total bituminous coal Texas lignite	10, 074 329, 947	5, 282 18 7, 379	126	(15)	15, 482 337, 326	3. 41 . 84	57 154	30	11 18	68 202	94 180	6, 405 36, 301	2. 42 9. 29
Total Texas	340, 021	18 12, 661	126	(15)	352, 808	. 95	211	30	29	270	158	42, 706	8. 26
		·	· · · · · · · · · · · · · · · · · · ·	·	UTAE	[				· · · · · · · · · · · · · · · · · · ·	<del></del>		
Carbon Emery Summit Other counties (Grand, Iron, Sevier, and Unitah)	2, 820, 774 656, 354 26, 244 39, 742	326, 604 105, 991 21, 717 23, 959	17, 598 4, 292 1, 132	18 27, 150 5, 066 35 28	3, 192, 126 771, 703 49, 128 63, 822	\$2. 35 2. 27 2. 01 2. 56	1, 539 308 34 45		561 129 16	2, 100 437 50 58	202 218 277 224	424, 667 95, 328 13, 867	7. 52 8. 10 3. 54 4. 91
Total Utah	3, 543, 114	478, 271	23, 115	18 32, 279	4, 076, 779	2. 33	1, 926		719	2, 645	207	546, 872	7. 45

Table 40.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States in 1941—Continued

[Exclusive of mines producing less than 1,000 tons]

		Disposition of	f coal produc	ed (net tons)			Ave	rage numbe	er of emplo	yees			
		Shipped	Used by mine em-	Used at mine for		Average		Suri	ace		Average number	Number of	Average
County	Loaded for shipment by rail or water <sup>1</sup>	by truck or wagon (excluding coal used by mine employees)	ployees, taken by locomotive tenders at tipple, or other uses at mine <sup>2</sup>	power and heat or made into beehive coke at mine	Total quantit <b>y</b>	value per ton 3	Under- ground	In strip pits	All others	Total	of days mines were active	man-days worked	tons per man per day
					VIRGIN	TA.							
Buchanan Dickenson Lee Scott Tazewell	5, 520, 947 2, 045, 350 1, 407, 626 3, 731, 744	10, 154 21, 727 84, 065 26, 862 56, 564	19, 348 7, 422 11, 619 40 27, 574	2, 995 772 2, 044 100 11, 125	5, 553, 444 2, 075, 271 1, 505, 354 27, 002 3, 827, 007	\$2. 32 2. 26 2. 49 2. 82 2. 45	3, 859 1, 925 1, 726 64 3, 517		442 223 255 14 564	4, 301 2, 148 1, 981 78 4, 081	219 262 220 218 221	942, 880 562, 461 436, 622 17, 006 902, 070	5. 89 3. 69 3. 45 1. 59 4. 24
Wise. Other counties (Chesterfield, Montgomery, and Russell)	3, 610, 408 1, 096, 471	90, 617 86, 966	24, 445 8, 828	19 530, 474 4, 659	4, 255, 944 1, 196, 924	2. 21 2. 29	4, 217 1, 099	4	543 216	4, 760 1, 319	222 231	1, 057, 546 304, 688	4. 02 3. 93
Total Virginia	17, 412, 546	376, 955	99, 276	19 552, 169	18, 440, 946	2. 33	16, 407	4	2, 257	18, 668	226	4, 223, 273	4. 37
· · · · · · · · · · · · · · · · · · ·					WASHING	TON							
King Kittitas Lewis Pierce Other counties (Thurston	344, 294 821, 626 6, 629 7, 069	289, 325 23, 425 27, 974 13, 001	5, 070 79, 511 90 132	542 11, 005 312 24	639, 231 935, 567 35, 005 20, 226	\$3. 76 3. 37 2. 74 4. 29	694 730 27 20	6	156 209 6 4	856 939 33 24	228 241 197 229	195, 228 226, 228 6, 514 5, 503	3. 27 4. 14 5. 37 3. 68
and Whatcom)	159, 883	46, 992	1, 161	3, 209	211, 245	3. 51	241		67	308	158	48. 656	4. 34
Total Washington	1, 339, 501	400, 717	85, 964	8 15, 092	1, 841, 274	3. 52	1,712	6	442	2, 160	223	482, 129	3. 82

	استمسا				ا ممم بنيد ما	44.00		**			004	000 000	- ^-
Barbour	1, 463, 451	8, 398	2, 771	70	1, 474, 690	\$1.88	1, 197		177	1,374	204	280, 638	5. 25
Boone	4, 520, 623	674	18, 180	1, 432	4, 540, 909	2. 25	3, 280		612	3, 892	214	832, 868	5. 45
Braxton	9,043	4,773	15	200	14, 031	1.88	31		11	42	104	4, 357	3. 22
Brooke	759, 277	371, 534	901, 872	90	2, 032, 773	1.87	908	97	209	1, 214	234	<b>2</b> 83, 700	8 7. 17
Clay.	694, 454	3, 705	12, 579	23, 933	734, 671	2, 22	483		124	607	268	162, 374	4. 52
Fayette	12, 436, 149	22, 922	383, 772	20 396, 110	13, 238, 953	2.44	11, 315		1,813	13, 128	227	2, 976, 459	4. 45
Gilmer	50, 832	2, 755	18		53, 605	1. 93	62		13	75	226	16.955	3. 16
Grant	3,987	61, 579	274	97	65, 937	2. 42	114		25	. 139	261	36, 258	1.82
Greenbrier	2, 155, 551	81, 805	9, 698	734	2, 247, 788	2.37	1,920		221	2, 141	229	490, 862	4. 58
Hancock	29, 806	136, 640	90	1, 133	167, 669	1.81	42	27	16	85	208	17, 698	8 9. 47
Harrison	5, 088, 898	37, 873	64, 398	2, 820	5, 193, 989	1.94	2,612	49	590	3, 251	219	712, 209	8 7, 29
Kanawha	7, 998, 338	72, 926	50, 035	6, 869	8, 128, 168	2.18	6, 439		826	7, 265	233	1, 694, 302	4.80
Lewis.	1, 530	16, 607	500		18, 637	1.80	18		4	22	261	5, 750	3. 24
Logan	19, 295, 907	7, 963	101, 116	4,082	19, 409, 068	2. 12	10, 196		2,308	12, 504	220	2, 752, 892	8 7. 05
McDowell	26, 173, 848	42, 834	317, 787	83, 017	26, 617, 486	2.37	18, 389		3,741	22, 130	231	5, 106, 583	5. 21
Marion		57, 782	247, 373	38, 472	10, 386, 913	1. 97	5, 571		924	6, 495	236	1, 534, 766	8 6. 77
Marshall	484, 098	130, 214	181, 447	3, 277	799, 036	2, 20	526		72	598	247	147, 737	5. 41
Mason	56, 176	35, 702	11, 949		103, 827	1.99	124		43	167	208	34, 799	2.98
Mercer		24, 168	28, 056	954	3, 686, 080	2.47	3, 132		720	3,852	230	887, 085	4.16
Mineral		34, 158	476	250	186,000	2, 61	216	6	51	273	224	61, 143	3.04
Mingo	4, 171, 436	4, 260	26, 868	120	4, 202, 684	2, 16	3, 129		547	3, 676	215	792, 066	5. 31
Monongalia	9, 613, 907	86, 972	32,008	311	9, 733, 198	1.91	4,079	24	1,019	5, 122	243	1, 244, 876	8 7. 82
Nicholas	189, 197	63, 990	5, 150		258, 337	2. 12	270		39	309	227	70, 286	3.68
Ohio	1, 746, 413	199, 099	2, 025	10	1, 947, 547	2.00	1, 543		165	1,708	262	446, 870	4.36
Preston	1, 222, 945	5, 167	133, 678	20 68, 215	1, 430, 005	2.06	1. 183	45	225	1, 453	234	340, 256	4. 20
Putnam	350, 558	8,994	1, 925	56	361, 533	2, 27	649		56	705	146	102, 641	3. 52
Raleigh		44, 363	112, 340	50, 211	14, 446, 930	2.44	11, 548		2,062	13, 610	225	3, 063, 011	4.72
Randolph		65, 648	5, 689	20, 973	1, 617, 349	2. 28	1, 232		260	1, 492	231	344, 724	4.69
Taylor		17, 176	224	1	578, 856	1.92	445		64	509	219	111, 648	5. 18
Tucker		4,622	3, 339	20, 206	605, 598	2. 51	511		78	589	213	125, 654	4.82
Upshur		22, 391	555	3, 340	309, 659	1.94	153		64	217	242	52, 541	5. 89
Wayne	124, 723	25, 930	1	l	150, 653	1.79	123		34	157	204	32, 054	4.70
Webster	1, 250, 630	6, 878	820	3,014	1. 261, 342	2.48	950		179	1, 129	225	254, 217	4.96
Wyoming	4, 191, 827	7, 260	24, 508	22,732	4, 246, 327	2. 58	3, 320		499	3, 819	232	886, 906	4. 79
Total West Virginia	135, 098, 222	1, 717, 762	2, 681, 535	20 752, 729	140, 250, 248	2. 23	95, 710	248	17, 791	113, 749	228	25, 907, 185	5. 41

Table 40.—Production, value, employment, days active, man-days, and output per man per day at bituminous-coal and lignite mines in the United States in 1941—Continued

[Exclusive of mines producing less than 1,000 tons]

		Disposition of	of coal produc	ced (net tons	)		Ave	rage numb	er of emplo	yees			
County	Loaded for shipment by rail or water 1	Shipped by truck or wagon (excluding coal used by mine employees)	Used by mine employees, taken by locomotive tenders at tipple, or other uses at mine?	Used at mine for power and heat or made into beehive coke at mine	Total quantity	Average value per ton 3	Under- ground	In strip	All others	Total	Average number of days mines were active	Number of man-days worked	Average tons per man per day
					WYOMI	NG		•					
Carbon Converse Fremont Hot Springs Johnson Lincoln Sheridan Sweetwater Other counties (Big Horn, Campbell, Natrona, Park, and Uinta)	694, 103 17, 416 63, 173 439, 669 562, 410 4, 436, 932 101, 559	39, 367 11, 848 11, 476 20, 483 10, 799 34, 594 31, 462 11, 528	2, 813 20 306 360 110 4, 513 3, 340 24, 049	18, 442 355 5, 304 1, 157 340 7, 521 1, 234 47, 607	754, 725 12, 223 34, 502 85, 173 11, 249 486, 297 598, 446 4, 520, 116	\$2. 03 2. 26 2. 55 3. 30 1. 95 2. 63 1. 79 2. 08	280 3 22 111 10 377 177 2, 403	26 9 3 3	93 1 10 25 4 119 60 513	399 13 32 136 14 496 240 2, 916	232 168 206 120 252 182 204 205	92, 495 2, 184 6, 589 16, 266 3, 523 90, 125 49, 002 597, 139	8. 16 5. 60 5. 24 5. 24 3. 19 5. 40 12. 21 7. 57
Total Wyoming	6, 315, 262	201, 534	36, 354	<sup>5</sup> 93, 180	6, 646, 330	2. 09	3, 407	56	847	4, 310	203	874, 568	8 7. 60

<sup>1</sup> Includes coal loaded at mine directly into railroad cars or river barges, hauled by truck to railroad siding for shipment by rail, and hauled by truck to waterway for shipment by water.

No coal was made into beehive coke at mines in 1941.

Includes coal transported from mines to points of use by conveyor, chute, or aerial tramway.

Nalue received or charged for coal f. o. b. mine, including selling cost. (Includes a value for coal not sold but used by producer, such as mine fuel and coal coked [not coke] as estimated by producer at average prices that might have been received if such coal had been sold commercially.)

Includes 4,830 tons made into beehive coke at mines in Jefferson County, Ala., in 1941.

Includes 124,198 tons made into beehive coke at mines in Las Animas County, Colo., in 1941.

'Other counties' in Illinois include Bond, Crawford, Greene, Hancock, Jefferson, Logan, McDonough, Macon, Marion, Marshall, Montgomery, Tazewell, Wabash, Warren, Will, and Woodford.

Much of the output is obtained from strip pits or by use of loading machines, in which types of operations production per man per day is large.

Production of Home Riverside and Alston mines is credited to Missouri, and production of Hume-Sinclair (Tiger mine) is credited to Kansas.

10 Output obtained chiefly from strip pits, in which production per man per day is large.

- 11 Includes 3,424 tons made into beehive coke at mines in Jackson County, Ky., in 1941.

  12 "Other counties" in Eastern Kentucky include Elliott, Leslie, McCreary, Madison, Magoffin, Morgan, and Owsley.

  13 "Other counties" in Missouri include Cedar, Chariton, Clark, Dade, Daviess, Grundy, Howard, Jasper, Johnson, Lincoln, Moniteau, Monroe, and Morgan.

  14 "Other counties" in Montana bituminous coal include Blaine, Fergus, Flathead, Gallatin, Judith Basin, Park, Phillips, and Pondera.

  15 In North Dakota some lignite "made into briquets" is included with "Other uses at mine." In South Dakota a small amount of colliery fuel is included with "Shipped by truck or wagon."

  16 Includes coal made into beehive coke at mines in the following counties in Pennsylvania in 1941: Cambria, 109,623 tons; Fayette, 4,371,446 tons; Greene, 7,635 tons; Indiana,

  305,201 tons; and Westmoreland, 1,243,842 tons—a grand total of 6,037,747 tons.

  17 Includes 20,108 tons made into beehive coke at mines in Grundy County, Tenn., in 1941.

  18 Includes 20,108 tons made into beehive coke at mines in Carbon County, Utah, in 1941.

  19 Includes 20,067 tons made into beehive coke at mines in Wise County, Va., in 1941.

  19 Includes 20,108 tons made into beehive coke at mines in Wise County, Va., in 1941.

  19 Includes coal made into beehive coke at mines in the following counties in West Virginia in 1941: Fayette, 347,934 tons; Preston, 65,318 tons—a grand total of 413,252 tons.

# STATISTICS ON LIGNITE IN 19412

### PRODUCTION

The statistics in this chapter on the lignite industry in the United States were compiled by the Bureau of Mines from annual reports received from producers of lignite in the areas mapped as lignite in Geological Survey Professional Paper 100-A, The Coal Fields of the United States. Subbituminous coal, sometimes called black lignite,

is not included in these statistics.

The production of lignite continued to decline in 1941, amounting to 2,775,832 net tons compared with 2,939,201 tons in 1940 and 3,042,537 tons in 1939. These figures do not include the output from some mines producing less than 1,000 net tons annually. The average value per net ton was \$1.24 in 1941, an increase from \$1.16 per ton in 1940. The number of employees in 1941 totaled 1,644, compared with 2,070 in 1940; and the average output per man per day, based upon calculated man-days, was 9.54 net tons, ranging from a low of 3.44 tons in Montana to a high of 10.23 tons in North Dakota. The industry worked an average of 177 days in 1941 and 178 days in 1940. The length of the working day in most of the mines was 8 hours, although some mines reported a 7-hour day to the Bureau, and a few, a 9-hour day.

North Dakota produced 83 percent of the total United States output of lignite in 1941; Texas followed with 12 percent, and the output of South Dakota and Montana taken together totaled 5 percent. In 1940 the North Dakota production represented 75 percent of the total, that of Texas 21 percent, and South Dakota and Montana

combined 4 percent.

For 1941 the Bureau of Mines received reports from 195 lignite mines. Of the total output of the industry, 6 mines, producing 200,000 to 500,000 net tons each, supplied 62 percent; 1 mine reporting production of 100,000 to 200,000 tons, 6 percent; 5 with an output of 50,000 to 100,000 tons each, 13 percent; 12 in the 10,000- to 50,000-ton class, 8 percent; and 171 mines producing less than 10,000 tons each, 11 percent. North Dakota, with 155, had the greatest number of mines. Montana was next, with 20 mines, and South Dakota and Texas followed, with 14 and 6, respectively.

Strip-pit operations were the source of 60 percent of the total production of lignite in 1941, whereas only 13 percent of the total Pennsylvania anthracite production was mined by this method and about 10 percent of the bituminous-coal output was recovered from

strip pits.

According to the Federal Power Commission, 842,250 net tons of lignite were used in 1941 for generating electric energy in the United States; this tonnage was equivalent to 30 percent of the total 1941 production. The consumption in the West North Central Division was 583,954 tons, and the West South Central and Mountain Divisions consumed 250,262 and 8,034 tons, respectively.

The following tables contain detailed statistics for lignite in 1941. Statistics of the lignite industry in 1942 were not available for inclusion in this chapter but may be obtained in mimeographed form upon request to the Coal Economics Division of the Bureau of Mines.

<sup>&</sup>lt;sup>2</sup> Compiled by J. A. Corgan and A. V. Coleman, Coal Economics Division, Bureau of Mines.

**Table 41.**—Summary of production, value, men employed, days operated, man-days of labor, and output per man per day at lignite mines in the United States in 1941, by States

	North Dakota	Texas	South Dakota	Montana 1	Total
Production (net tons):					
Loaded at mines for shipment  Commercial sales by truck or wagon  Used by employees, taken by locomo-	1, 709, 100	329, 947	37, 338	4, 483	2, 080, 868
	411, 880	2 7, 379	33, 364	54, 042	506, 665
tives at tipple, and other uses	<sup>8</sup> 163, 515 24, 393	(2)	4 123 (4)	228 40	163, 866 24, 433
Total production: 1941	2, 308, 888	337, 326	70, 825	58, 793	2, 775, 832
	2, 218, 434	606, 418	66, 085	48, 264	2, 939, 201
Value: Total: 1941  1940  A verage per ton: 1941  1940	\$2,937,000	\$284,000	\$108,000	\$105,000	\$3, 434, 000
	\$2,587,000	\$637,000	\$88,000	\$86,000	\$3, 398, 000
	\$1,27	\$0.84	\$1.52	\$1.79	\$1. 24
	\$1,17	\$1,05	\$1.33	\$1.78	\$1. 16
Number of employees: Underground. Surface (including strip pits)	562	154	15	68	799
	713	48	54	30	845
Total employees: 1941	1, 275	202	69	98	1, 644
	1, 377	546	63	84	2, 070
Average number of days mines operated: 1941. 1940.  Man-days of labor: 1941 <sup>5</sup> Average output per man per day: 1941 <sup>5</sup>	177	180	174	174	177
	182	170	168	161	178
	225, 657	36, 301	12, 001	17, 083	291, 042
	10, 23	9, 29	5, 90	3, 44	<b>9.</b> 54

Includes output of Custer, Dawson, McCone, Richland, Roosevelt, Sheridan, and Valley Counties.
 Some colliery fuel is included in "Commercial sales by truck or wagon."
 Includes some lignite "made into briquets."
 Some colliery fuel is included in "Other uses."
 Based upon calculated number of man-days.

Table 42.—Production, value, men employed, days operated, man-days of labor, and output per man per day at lignite mines in the United States in 1941, by States and counties MONTANA

		212 011					
	Total	Va	lue	Total		Average	Average
County	produc- tion (net tons)	Total (thou- sand dollars)	Average per ton	number of em- ployees	Man-days of labor <sup>1</sup>	number of days mine operated	tons per man per day 1
Custer, Dawson, and Valley McCone Richland and Roosevelt Sheridan		33 6 36 30	\$1.68 1.74 2.27 1.51	28 13 31 26	4, 605 1, 752 5, 660 5, 066	164 135 183 195	4. 27 1. 97 2. 80 3. 91
Total	58, 793	105	1. 79	98	17, 083	174	3.44
		NORTH	DAKOT	A			
Adams and Billings Bowman Burke. Burleigh Divide Dunn Golden Valley Grant. Hettinger McKenzle McLean Mercer Morton Mountrail Oliver Slope and Stark Ward Williams	283, 251 181, 464 5, 655 7, 296 12, 807 13, 454 3, 629 131, 935 656, 773 23, 943 11, 863 10, 382 116, 171 470, 079 25, 359	103 16 356 357 221 8 11 18 6 189 820 32 18 10 136 580 38	\$1.55 1.65 1.28 1.22 1.41 1.51 1.51 1.34 1.65 1.43 1.25 1.34 1.52 1.34 1.52	92 16 76 85 55 15 12 26 32 7 113 284 49 23 13 89 236 52	14, 985 2, 445 12, 617 17, 677 12, 850 1, 475 1, 860 2, 484 8, 294 855, 741 5, 135 3, 640 2, 000 22, 198 41, 992 6, 950	163 153 208 234 28 155 96 103 122 172 189 105 158 154 249 178	4. 45 3. 96 2 22. 07 2 16. 02 2 14. 12 3. 3. 92 5. 16 6. 78 12. 22 6. 78 12. 22 2 11. 19 5. 23 2 11. 19
Total	2, 308, 888	2, 937	1.27	1, 275	225, 657	177	10. 23

Table 42.—Production, value, men employed, days operated, man-days of labor, and output per man per day at lignite mines in the United States, in 1941, by States and counties—Continued

#### SOUTH DAKOTA

					1.0		
	m. 4-1	Va	lue	m / 1		Average	
County	Total produc- tion (net tons)	Total (thou- sand dollars)	Average per ton	Total number of em- ployees	Man-days of labor <sup>1</sup>	number of days mine operated	Average tons per man per day i
Corson and Dewey	65, 730 2, 127 2, 968	99 4 5	\$1.51 1.88 1.68	47 10 12	9, 732 1, 075 1, 194	207 108 100	6. 75 1. 98 2. 49
Total	70, 825	108	1. 52	69	12, 001	174	5. 90
		TEX	KAS				
Bastrop and Milam Henderson and Titus	79, 191 258, 135	39 245	\$0.49 .95	75 127	5, 670 30, 631	76 241	3 13. 97 8. 48
Total	337, 326	284	.84	202	36, 301	180	9. 29

### NUMBER AND SIZE OF MINES

Table 43.—Number and production of lignite mines in the United States, in 1941, classified by size of output

	Mir	ies	Production			
Class	Number	Percent	Tôtal (net tons)	Average per mine (net tons)	Percent	
1 (200,000-500,000 tons) 2 (100,000-200,000 tons) 3 (50,000-100,000 tons) 4 (10,000-50,000 tons) 5 (Under 10,000 tons) Total	6 1 5 12 171 195	3. 1 . 5 2. 6 6. 1 87. 7	1,710,669 177,624 358,414 219,442 309,683 2,775,832	285, 112 177, 624 71, 683 18, 287 1, 811	61. 6 6. 4 12. 9 7. 9 11. 2	

#### METHODS OF RECOVERY

Table 44.—Lignite mined by different methods in the United States in 1941, by States, in net tons

State	Mined by hand	Shot off the solid	Cut by machines 1	From strip pits	Total
Montana North Dakota South Dakota Texas	<sup>2</sup> 14, 818 7, 161 . 150 ( <sup>2</sup> )	<sup>2</sup> 291, 195 188, 754 4, 245 ( <sup>2</sup> )	13, 434 585, 829	2 76, 672 1, 527, 144 66, 430 (2)	58, 793 2, 308, 888 70, 825 337, 326
Total	22, 129	484, 194	599, 263	1, 670, 246	2, 775, 832

<sup>&</sup>lt;sup>1</sup> A total of 20 machines was used—11 "permissible" and 9 of other types.

#### STRIPPING OPERATIONS

The output of lignite from strip pits in 1941 amounted to 1,670,246 tons, compared with 1,512,308 tons in 1940. Lignite produced by this method of mining represented 60 percent of the total output of the industry in 1941 and 51 percent in 1940. As for many years in the

Based upon "calculated" man-days.
 Output is obtained chiefly from strip pits, in which production per man per day is large.

<sup>&</sup>lt;sup>2</sup> Montana includes Texas.

past, the largest producer of lignite from strip pits was North Dakota, whose output in 1941 was 1,527,144 tons compared with a combined total of 143,102 tons from Texas, Montana, and South Dakota.

Detailed statistics for stripping operations in the lignite industry in

1941 are given in table 45.

Table 45.—Summary of stripping operations that produced lignite in the United States in 1941, by States

		Number of shovels.		Total	A		nber of ployees		Aver- age		Aver-
State	Num- ber of strip pits 1	dragline excava- tors, and coal- loading ma- chines <sup>2</sup>	Coal mined by stripping (net tons)	value at mines (thou- sand dollars)	A ver- age value per ton	In strip pits	All others	Total	num- ber of days mines oper- ated	Man- days of labor *	tons per man per day
Montana and Texas North Dakota. South Dakota.	4 67 8	7 46 7	76, 672 1, 527, 144 66, 430	41 1,898 101	\$0.53 1.24 1.52	38 444 44	1 92 7	39 536 51	73 175 195	2, 847 93, 878 9, 962	26. 93 16. 27 6. 67
Total	79	60	1, 670, 246	2, 040	1. 22	526	100	626	170	106, 687	15. 66

# IMPORTS AND EXPORTS 1

Table 46.—Bituminous coal 2 imported for consumption in the United States, 1941-42, by countries and customs districts, in net tons

	1941	1942		1941	1942
COUNTRY			CUSTOMS DISTRICT—continued		
North America:		400 050	Duluth and Superior	1, 494 2, 016	377
Canada Mexico.	71, 041	493, 953 215	Galveston Maine and New Hampshire	195, 847	175, 434
Europe: United Kingdom  Africa: Union of South Africa	319, 008	2, 753 560	Maryland Michigan	179	379
Airies: Omon of South Airies			Montana and Idaho	140, 796	247, 837
	390, 049	497, 481	New York		2,772
CUSTOMS DISTRICT			Philadelphia St. Lawrence Vermont	1, 953 376 865	12
Alaska	4, 291	9, 763	Virginia		597
Buffalo	-,	37	Washington	41, 392	60,058
Chicago Dakota Dakota	831	215		390, 049	497, 481

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.
<sup>2</sup> Includes slack, culm, and lignite.

Includes some pits in which the stripping is done by hand.
 In some cases the same equipment was used for stripping or excavating and for loading the coal; this duplication has been eliminated. In some cases the coal was excavated by machine and loaded by hand.
 Based upon calculated man-days.

Table 47.—Exports of bituminous coal to Canada and Mexico, the West Indies, and Central America, and "overseas" destinations, 1938-42, in thousands of net tons

				"Ove	erseas" (a	all other	countries	3)		
Year	Canada and Mexico	West Indies and Central America		South America	Europe	Asia.	Africa	Oceania	Total "over- seas"	Grand total
1938	9, 561 9, 976 13, 537 18, 196 21, 008	619 599 455 332 440	23 76 106 186 90	247 681 1,660 1,541 925	11 165 653 370 263	29 91 29 25 4	2 26 62 204	28	310 1, 015 2, 474 2, 212 1, 486	10, 49 11, 59 16, 46 20, 74 22, 93

<sup>&</sup>lt;sup>1</sup> Includes Bahamas and Panama.

Table 48.—Bituminous coal exported from the United States, 1941-42, by countries, in net tons 1

Country	1941	1942	Country	1941	1942
North America:			South America—Continued.		-
Bermuda	4,860	4, 477	Paraguay	12	
British Honduras	131	7, 71	Peru	99	
Canada			Surinam		7.634
Canada	18,194,909	21,000,779	Surmain	4, 142	
Central America: Costa Rica	1 700	- 00	Uruguay	120, 463	79, 098
Costa Rica	1,593	20	Uruguay Venezuela Other South America	354	
El Salvador	56	34	Other South America	1, 123	1, 220
Guatemala	296				
Honduras	582	164		1, 540, 838	925, 108
Nicaragua	53	4			
Panama:			Europe:		1
Canal Zone	65, 182	100, 313	Portugal	353, 721	244, 934
Republic of	15	13	Spain	2,670	
Greenland	228	668	Spain Switzerland	6,804	
Iceland.		2, 145	Other Europe	6, 878	18, 390
Mexico	661	964	O UZOT ZIGIOPOTITITITI	0,010	10,000
Newfoundland and Labra-	001	001		370, 073	263, 324
dor	181, 443	82, 579		010,010	200, 021
West Indies:	101, 110	02,018	Asia:		
British:		1	Irag		0.000
Barbados	624	0 714	Netherlands Indies		3, 932
	024	3,714	Netherlands Indies	13, 627	
Jamaica	22, 551	33, 158	Philippine Islands	6, 793	
Trinidad and Tobago Other British	27, 871	95, 160	Other Asia	4, 426	10
Other British	2,611	56			
Cuba	177, 044	197, 156		24,846	3, 942
Curacao (N. W. I.)	2,967	530			
Dominican Republic	118	98	Oceania	28, 840	
French	30, 106	8,940			
Haiti		7	Africa:	2.5	i
			Canary Islands	22, 236	7, 202
	18,713,951	21, 537, 117	Egypt		152, 597
			Liberia		11
South America:			Morocco	22, 637	44. 284
Argentina	343, 029	172, 988	Union of South Africa	1, 792	1,
Bolivia	31, 375	30,076	Other Africa	15, 258	30
Brazil	981, 842	611, 307	Outof Affica	10, 200	30
Chile	58, 205	22, 492	-	61, 923	204, 124
Colombia	55	22, 492		01, 925	204, 124
Colombia	139	271	Comment deaded	00 540 451	00 000 015
Ecuador	199	2/1	Grand total	20,740,471	22, 933, 615

<sup>&</sup>lt;sup>1</sup> Amounts stated do not include fuel or bunker coal loaded on vessels engaged in the foreign trade, which aggregated 1,643,010 tons in 1941 and 1,584,763 tons in 1942.

Table 49.—Bituminous coal exported from the United States, 1941-42, by customs districts, in net tons

Customs district	1941	1942	Customs district	1941	1942
North Atlantic:			Pacific Coast—Continued.		
Maine and New Hampshire.	6, 527	1,817	San Diego	90	92
Massachusetts	76	2, 363	San Francisco	35	
New York	9, 445	122, 713	Washington		1,046
Philadelphia	47, 247	44, 566	Northern border:		
South Atlantic:			Buffalo	1, 131, 767	1, 495, 223
Maryland	302, 757	222, 175	Chicago	1,695	179, 047
South Carolina	28, 902	1,147	Dakota	6,066	
Virginia	2,073,528	1, 263, 533	Duluth and Superior	20,086	
Gulf Coast:	1	' '	Michigan	2, 027, 566	1, 669, 816
Florida	9, 307	88, 123	Montana-Idaho	326	49
Mobile	11, 448	111, 363	Ohio	10,631,883	11, 243, 027
New Orleans	1,556	11, 423	Rochester	2, 939, 606	
Mexican border:			St. Lawrence	1, 470, 355	
Arizona	292	362	Vermont	16,886	8,557
El Paso	75	188	Wisconsin	685	1,061
Laredo	19	217	Miscellaneous: Alaska	96	528
Pacific Coast:					I
Oregon	2, 150			20,740,471	22, 933, 615

Shipments to Alaska, Hawaii, Puerto Rico, and Virgin Islands.—In addition to export trade proper, the United States supplies a small tonnage of anthracite and bituminous coal to Alaska, Hawaii, Puerto Rico, and the Virgin Islands. Shipments in 1941–42 are shown in the following table.

Table 50.—Shipments of bituminous coal to noncontiguous Territories, 1941-42

			1941		1942	
	Territory		Net tons	Value	Net tons	Value
Alaska: Anthracite			} 21, 805 1, 466 16, 185 132, 128	\$218, 029 34, 623 80, 691 591, 242	9, 812 469 11, 150 39, 368	\$205, 255 8, 775 62, 435 201, 741

# WORLD PRODUCTION

Table 51.—World production of coal and liquite, 1938–42, by countries, in thousands of metric tons  $^{\rm 1}$ 

[Compiled by B. B. Waldbauer, Bureau of Mines]

Country 1	1938	1939	1940	1941	1942
orth America:					
Canada:	9, 815	10, 985	12,638	12,872	12, 98
Lignite	3, 153	3,094	3, 298	3,662	4, 10
Greenland	7	(2)	6	(3)	(8)
Mexico	893	628	816	856	90
United States:			40 500	77 100	
Anthracite	41,820	46, 708	46,706	51, 136	54, 7
Bituminous	313, 473 2, 720	355, 445 2, 760	415, 336 2, 666	466, 426 2, 518	<b>526, 1</b>
Ligniteuth America:	2, 120	2, 100	2,000	2,010	,
Brazil	883	1,047	1, 336	1,408	4 1, 8
Chile	2,044	1,850	1,937	1, 408 2, 051	1,9
Colombia	331	349	521	403	(8)
Peru	75	108	153	195	``*1
Venezuela	6	3	5	4	
rope:				<i>a</i>	(9)
Albania: Lignite	20 505	(2) 29, 847	(3)	(3)	(3)
Belgium	29, 585	29,847	(9)	(9)	
Bulgaria: Coal	142	164	188	(3)	(3) 4 2, 8
Lignite	1,855	2, 134	2,700	(3) (3)	42.8
Czechoslovakia:	1,000		1		_, -
Coal	15,800	(2) 5 779	(8) 6 805 118	(3) 6 816 155	(3) 6 1, 0
Lignita	14, 717	8 779	6 805	6 816	61,0
Eire	120	120			(3) (3)
Faroe Islands: Lignite	8	. 8	(3)	(3)	(8)
riance.	40, 400				
Coal	46, 498 1, 057	<b>51,000</b>	(3)	(3)	(3)
Lignite	1,007	, ,			
Germany: Coal	186 177	200,000	(3)	(3)	7 139, 0
Lignite	186, 177 195, 312	230,000	(3) (3)	(3) (3)	(3)
Austria:	200,022		· · · · ·	``	
Coal	227	(2) (2)	(3)	(3)	(3) (3)
Lignite	3, 342	(2)	(3)	(3)	(3)
Greece: Lignite	108	139	(3)	(3) (3) 4 180	4 3
Hungary:	1 040		1 007	(8)	(3)
Coal	1,042 8,317	1, 107	1, 207 9, 485	(3)	(3) (2)
Lignite Italy:	8, 517	9, 518	9,400	(9)	· (5)
Coal	1,480	2,025	(3)	(3)	(3)
Lignite	873	1,058	(3)	(3)	(3) (3)
Netherlands:	0.0	2,000			- 1
Coal	13, 488	12,861	(3)	(3) (3)	(3) (3)
Lignite	171	197	(3)	(3)	(3)
Poland:				(0)	én.
Coal	38, 104	(2) (2)	(3) (3)	(3) (3)	(3) (3)
Lignite	10	(2)	(0)	(9)	(9)
Portugal:	299	313	310	460	. 8 3
Coal Lignite	15	35	67	93	8
Rumania:	10		) "		
Coal	299	285	(3)	(3)	۱ ، ه ،
Lignite	2,097	2, 300	(3)	(3) (3)	} 46,8
Spain:	•		1		
Coal	5, 649	6, 755	8,849	8,775	9 5, 3
Lignite	166	205	568	819	9 (
Svalbard (Spitsbergen)	627	640	(3) 498	(³) 583	(3)
SwedenSwitzerland	431 3	444 3	8	(3)	(3)
Switzerland United Kingdom:	0	9	°	(9)	(-)
Great Britain	230, 659	236, 700	4 233, 700	4 216, 800	4 215, 9
Northern Ireland	(10)	(2)	(3)	(3)	(3)
U. S. S. R.:	`, '				1
Coal	00 607	(2)	ſ 148, 700	(3) (3)	4 247, (
Lignite	98,627	(2)	148,700 15,900	(3)	- 221,0
Yugoslavia:	-	1			<b>(4)</b>
Coal	450	444	(3) 11 3, 170	(3) 11 2,600	(3) (3)
Lignite	5, 287	5, 622	11 3, 170	11 2,600	(4)
sia:	(10)	(10)	(2)		(3)
British Borneo	(10) (2)	(10)	(3)	(3) 12 6, 000 24, 500	(3)
China Manchuria	15,000	19,000	(3)	24, 500	(3)
VIAUCHUEIA	3, 200	4, 481	- (3)	(3)	(3)

A. C. S.

Table 51.—World production of coal and lignite, 1938-42, by countries, in thousands of metric tons —Continued

Country 1	1938	1939	1940	1941	1942
Asia—Continued.					
Federated Malay States	486	448	794	(3) 4 26,000	(3)
India, British	28, 798	28, 214	4 26,000	4 26 000	(3) (3)
Indochina:	20,		20,000	-0,000	
Coal	2, 340	2, 588	2, 456	13 1, 117	18 732
Lignite	2,010	2, 000	30	(3)	(3)
Japan:	. 1		- 00		()
Ignan proper		1	1		
Japan proper:	(2)	(2)	(3)	(3) (3) (3) (4) (4) (778 (3)	(3)
Lignite	(2) (2) (2)	(2) (2) (2)	(3) (3) (3)	28	(3)
Karafuto	\sigma_2\lambda	2	\dag{3}	(3)	\2\\.
Taiwan	2	(2)	\(\alpha\)	8	\ <del>2</del> \
Netherlands Indies	1, 457	1,781	2,009	14 779	0 0 0 0 0
Philippine Islands	41	47	(3), 003	(3)	λ.,
Syria and Lebanon: Lignite	(10)	1	(9)	(3)	\ <u>\</u> 2
Syria and Lebanon: Lignite	(10)	1	2	(9)	(*)
Turkey:	0.500	0.000	0.010	(m)	(0)
Coal	2, 589	2,696	3,019	(3)	(3) (3)
Lignite	129	151	280	(9)	(9)
U. S. S. R.: Coal	. 1		i i		
Coal	34, 261	(2)	(3)	(3)	(3)
Lignite	02,202				
Africa:			[		
Algeria	13	(2) (2)	50	72	(3) (3)
Belgian Congo: Coal	42		23	(3)	(3)
Morocco, French	123	116	143	145	4 110
Nigeria	368	311	313	(3)	(3) (3)
Portuguese East Africa	10	. 8	20	(3) (3) (3)	(3)
Southern Rhodesia	1,044	1,118	(3) 17, 176		(3)
Union of South Africa	16, 284	16,890	17, 176	8 16, 982	(3) 8 17, 403
Oceania:					
Australia:					
New South Wales	9, 725	11, 376	15 9, 551	18 11, 939	15 12, 497
Queensland	1, 131	1, 339	(3)	(3)	
Tasmania	85	99	(3)	(3)	(3) (3)
Victoria:			` '		
Coal	312	371	(3)	(3)	(3)
Lignite	3, 734	3, 710	(3)	(3) (3) (3)	(3) (3) (3)
Western Australia	614	566	548	785	: /s\
New Zealand:	011	000	010		
Coal	994	1,061	1, 163	1, 199	
Lignite	1, 264	1, 319	1,393	1, 483	2,709
Tylginio	1,201	1,010	1,000	1, 100	
Total, all grades	1, 469, 000	1, 639, 000	(3)	(3)	(3)
, ~		-			
Lignite (total of items shown above) Bituminous and anthracite (by subtrac-	264,000	301,000	(8)	(3)	(3)
tion)	1, 205, 000	1, 338, 000	(3)	(3)	(3)

<sup>1</sup> Coal is also mined in Argentina, Iran, and Italian East Africa, but production figures for these countries are not available.

2 Estimate included in total.

3 Data not yet available.

4 Estimated.

5 Bituminous coal.

6 Estimated production of Slovakia only.

7 Estimated production of Ruhr only.

8 January to Outober, inclusive.


9 January to July, inclusive.

10 Production less than 1,000 tons.

11 Estimated production of Croatia only.

12 Free China.

18 Free China.
18 January to June, inclusive.
18 Production of Government mines only.
15 Preliminary.



# PENNSYLVANIA ANTHRACITE

By J. A. CORGAN, J. W. BUCH, AND A. V. COLEMAN

### SUMMARY OUTLINE

	Page		Page
Review of 1942	913		
Definition of Pennsylvania anthracite in-		Sales realization	926
Statistical trends	914	Imports and exports	931
The war and anthracite	918		931
Federal Anthracite Coal Commission	918		
Anthracite Committee		Production	932
Anthracite Industries, Inc.	919		933
Anthracite Institute	919	Small mines and intercompany sales	935
Labor	920	Regions, fields, and counties	935
Research	920		
Competitive fuels in the United States and		Labor statistics	942
in principal markets	920		944
Transportation and distribution of anthra-		Mechanical loading	944
cite to principal markets	922		945
Consumption	924	Strip pit operations	
Changes in stocks			
Illicit coal			
Trend of employment	926		947
Trend in prices		World production	049

## REVIEW OF 1942

The accelerated demand for Pennsylvania anthracite in 1942 was created largely by the shortages of fuel oil and coke in the New England and Middle Atlantic States, and by increased industrial activity, expanded purchasing power, and rising exports, particularly to Canadian markets. The output of 60,328,000 net tons in 1942 was the largest since 1930 and represented an increase of 7 percent over the production of 56,368,000 tons in 1941; despite the increase of about 4,000,000 tons, the output was not sufficient to meet the demand for anthracite. In 1942 the contract between the producers and the United Mine Workers of America permitted the industry to work 40 weeks of 5 days each and 12 weeks of 6 days each. In January 1943 a 6-day week was inaugurated, and this increased working time should tend to alleviate somewhat the manpower shortage that existed in 1942; thus, should the demand for anthracite continue at the same level, the industry will be in a better position regarding working time than in 1942.

The Bureau of Mines cooperated closely with the Office of Solid Fuels Coordination for War in handling problems relating to production, consumption, distribution, utilization, and transportation of anthracite, bituminous coal, and coke.

Funds for research pertaining to the Pennsylvania anthracite industry's problems, to be expended at the direction of the Secretary of the Interior acting through the Bureau of Mines, were authorized in

December 1942 by the Congress, but no appropriation for the work

has yet been made available.

The Federal Anthracite Coal Commission, created by House Joint Resolution 255 to investigate economic conditions in the anthracite-producing areas of the United States, submitted its report to the President and the Congress in April 1942. The report recommended measures for both short-term and long-term improvements which are discussed elsewhere in this chapter.

The Anthracite Commission continued its functions relating to the production of anthracite, and through its efforts arrangements were made for legitimate companies to purchase "bootleg" coal lawfully and

to employ men formerly working in illicit operations.

Anthracite Industries, Inc., financially supported by producers representing more than 80 percent of the anthracite output, is working on the most extensive research program ever undertaken by the anthra-

cite industry.

The Anthracite Tidewater Emergency Bureau, a voluntary organization representing anthracite producers, wholesalers, and railroads delivering at tidwater points, was established at the suggestion of the Interstate Commerce Commission and the Car Service Division of the American Association of Railroads to expedite rapid turn-around movement of railroad cars at terminal piers. This newly formed Bureau compiles statistics concerning cars of coal standing at tidewater piers and endeavors to prevent undue detention of such cars, thereby assisting the railroads in meeting the increased demands for transportation due to the war. It is thought that the Bureau will bring about more efficient utilization of railroad equipment, boats, and barges at a time when full use of this equipment is urgently needed.

The failure of the anthracite operators and miners to agree upon terms of a new contract to supersede the agreement that expired on April 30, 1943, was followed by several stoppages of work and the loss of considerable tonnage. These developments and the bitter controversies arising therefrom received widespread attention, and the public has been fully advised of them by press and radio. They will be

detailed for the record in the 1943 edition of this chapter.

Definition of Pennsylvania anthracite.—Pennsylvania anthracite includes all nonbituminous coal mined in that State, and for historical purposes data on the output of the Bernice Basin in Sullivan County are included in this chapter, although the coal of this basin has been officially classified as semianthracite. The anthracite fields are in the northeastern part of the State, and the coal is mined in the following counties: Carbon, Columbia, Dauphin, Lebanon, Lackawanna, Luzerne, Northumberland, Schuylkill, Susquehanna, and Wayne.

Statistical trends.—Tables 1 and 2 present pertinent statistical data

on the Pennsylvania anthracite industry.

CARLED CARLES CONTRACTOR CONTRACT

Table 1.—Statistical trends of Pennsylvania anthracite industry, 1938-42

	1938	1939	1940	1941	1942
Production: Loaded at mines for shipment: Breakers net tons. Washeries do Dredges db Sold to local trade and used by	39, 010, 935 1, 679, 509 373, 425	1 43, 660, 662 1, 766, 384 565, 236	1 43, 800, 127 1, 761, 942 613, 884	46, 864, 422 2, 538, 692 1, 008, 983	51, 173, 756 1, 957, 926 778, 019
employeesnet tons_	2, 722, 206	3,081,073	3, 052, 626	3, 695, 125	4, 059, 403
Used at collieries for power and heat net tons	2, 312, 952	2, 414, 022	2, 256, 061	2, 261, 045	2, 358, 625
Total productiondo Value at breaker, washery, or dredge Average sales realization per net ton on breaker shipments; Domestic:	46, 099, 027 \$180, 600, 000	51, 487, 377 \$187, 175, 000	51, 484, 640 \$205, 490, 000	56, 368, 267 \$240, 275, 000	60, 327, 729 \$271, 673, 000
Lump and Broken  Egg. Stove Chestnut Pea Total domestic Steam:	\$5. 18 \$5. 33 \$5. 36	\$4. 63 \$4. 73 \$4. 84 \$4. 87 \$3. 65 \$4. 64	\$5.49 \$5.32 \$5.47 \$5.49 \$4.13 \$5.24	\$5. 72 \$5. 84 \$5. 93 \$5. 93 \$4. 50 \$5. 68	\$6. 03 \$6, 24 \$6. 26 \$6. 28 \$4. 85 \$6. 05
Buckwheat No. 1 Buckwheat No. 2 (Rice) Buckwheat No. 3 (Barley) Other, including Buckwheat No. 4 Total steam Total all sizes/	\$0.87	\$2. 90 \$2. 20 \$1. 62 \$0. 91 \$2. 25 \$3. 85	\$3. 18 \$2. 35 \$1. 68 \$0. 92 \$2. 41 \$4. 27	\$3. 37 \$2. 52 \$1. 78 \$1. 02 \$2. 55 \$4. 59	\$3. 46 \$2. 63 \$1. 89 \$1. 09 \$2. 58 \$4. 79
Percent by sizes in total breaker ship- ments: Domestic:	1 1 1 1 1				
Lump and Broken Egg Stove Chestnut Pea Total domestic	5. 4 23. 7 26. 0	0.6 5.2 24.1 25.8 11.0 66.7	0.3 4.5 24.1 25.9 11.1 65.9	0.3 4.2 24.3 25.5 10.8 65.1	0.3 5.2 23.6 24.9 9.6 63.6
Steam: Buckwheat No. 1 Buckwheat No. 2 (Rice) Buckwheat No. 3 (Barley) Other, including Buckwheat No. 4. Total steam Producers' stocks on Dec. 312 net tons. Exports do Imports Consumption (calculated)do.	54. U	14. 3 7. 8 8. 5 2. 7 33. 3 994,000 2, 590,000 298,000 49,700,000	14.7 7.8 8.8 2.8 34.1 939,000 2,668,000 135,000 49,000,000	14. 6 8. 2 8. 9 3. 2 34. 9 1, 274, 000 3, 380, 000 75, 000 52, 700, 000	14.5 8.0 9.6 \( \mathbb{V}\)4.3 36.4 798,000 4,439,000 141,000 56,500,000
Average number of days worked	579, 457 27, 435	241, 688 27, 795	186 176, 432 19, 464	397, 616 39, 768	239 279, 641 26, 631
Average number of men employed Output per man per daynet tons Output per man per yeardo Quantity cut by machinesdo Quantity mined by strippingdo	96, 417 2, 79 478 1, 588, 407 5, 095, 341	93, 138 3. 02 553 1, 881, 884 5, 486, 479	91, 313 3. 02 562 1, 816, 483 6, 352, 700	88, 054 3. 04 617 1, 855, 422 7, 316, 574	82, 121 2, 95 705 2, 285, 640 9, 070, 933
Quantity loaded by machines under- groundnet tons Distribution: Total receipts in New England 3	10, 151, 669	11, 773, 833	12, 326, 000	13, 441, 987	14, 741, 459
Exports to Canadado Loaded into vessels at Lake Erie 4	4, 468, 000 1, 896, 000	4, 902, 000 2, 577, 000	4, 822, 000 2, 627, 000	5, 551, 000 3, 361, 000	5, 974, 000 4, 418, 000
net tons Receipts at Duluth-Superior •.do	450, 000 155, 000	531, 000 202, 000	430, 000 138, 000	536, 000 253, 000	575, 000 222, 000

Includes small quantity of washery coal.
 Anthracite Committee. Figures represent prepared coal in ground storage; 1941 figures are through December 27; 1942 figures are through Jan. 3, 1943.
 Commonwealth of Massachusetts, Division on the Necessaries of Life.
 Ore and Ocal Exchange, Cleveland, Ohio.
 U. S. Engineer Office, Duluth, Minn.

Table 2.—Statistical summary of monthly developments in Pennsylvania anthracite industry in 1942

[All tonnage figures represent net tons]

							19	42							
													Yes	ar	
	Janu- ary	Febru- ary	March	April	Мау	June	July	August	Septem- ber	Octo- ber	Novem- ber	Decem- ber	Total	Change from 1941 (per- cent)	1941 (total)
Production, including mine fuel, local sales, and dredge coal:  Monthly total	4, 560, 000	4, 801, 000	5, 116, 000	5, 185, 000	4, 873, 000	5, 153, 000	5, 374, 000	5, 212, 000	5, 459, 000	5, 132, 000	4, 824, 000	4, 639, 000	60, 328, 000	+7.0	56, 368, 000
Shipments, breakers, and washeries only: Monthly total, all sizes Distribution:	3, 751, 707	3, 96 <b>9,</b> 257	4, 185, 411	4, 572, 156	4, 215, 351	4, 302, 793	4, 551, 595	4, 387, 242	4, 486, 023	4, 279, 337	4, 002, 680	3, 846, 217	50, 549, 769	+8.0	46, 798, 819
Lake Erie loadings <sup>2</sup> Receipts at Duluth-Superior <sup>8</sup> Upper Lake dock trade: <sup>4</sup>				55, 700 27, 720	65, 199 20, 675	78, 477 38, 092	50, 512 29, 370		78, 201 21, 010	51, 060 7, 312	130, 548 55, 901	203	575, 176 221, 793	+7. 2 -12. 3	536, 490 252, 951
Receipts: Lake Superior Lake Michigan	2,757	28 1,710		27, 719 22, 563	20, 675 46, 184	23, 001 34, 730	14, 138 22, 144	14, 632 29, 867	13, 877 25, 549	7, 386 30, 547	40, 136 60, 463	139 3, 594	161, 731 281, 502	-33.8 -2.9	244, 370 289, 987
Deliveries (reloadings):  Lake Superior  Lake Michigan  Retail yards—159 selected deal-	18, 656 25, 596				26, 597 48, 078	25, 393 34, 196			20, 412 23, 791	27, 969 26, 697	29, 924 14, 836	20, 758 23, 979	231, 218 325, 370	+19. 1 +13. 1	194, 112 287, 687
ers: Deliveries 4 New England receipts:6	296, 205	1	259, 331	346, 298	366, 150					202, 589	175, 687	287, 874			(8)
By tide (including imports) By rail Exports ' Imports '	38, 602 317, 830 222, 671 4, 944	435, 172 272, 169	465, 224 341, 731	378, 304 310, 219	81, 245 445, 536 335, 126 403	453, 294 284, 881	39, 341 461, 813 320, 758	40, 974 522, 676 379, 898 11, 432	538,006 724,088	478, 969	60, 364 460, 131 457, 968 15, 260		5, 393, 475 4, 438, 589	$ \begin{array}{r r} -14.8 \\ +10.8 \\ +31.3 \\ +88.5 \end{array} $	4, 869, 640 3, 380, 189
Industrial consumption by: Railroads (class I only) <sup>8</sup> Electric power utilities <sup>9</sup> Other industrial consumers <sup>10</sup>	117, 242 228, 850	94, 276 210, 760		105, 690 207, 272	93, 899 228, 149		81, 437 259, 594	82, 367 257, 017	82, 830 256, 750	97, 712 247, 423	103, 230 221, 427	119, 536 240, 958		-13.7 -3.1	
(selected represented plants only)	134,026							94, 042 67			121, 450 76	128, 533 75			(5) (5)
Stocks at end of period shown: Railroads (class I only)	180, 690			154, 763								-		-18. 2	1 1 1 1 1

Other industrial consumers 10	1, 202, 096	1, 148, 671	1, 170, 580	1, 215, 320	1, 293, 276	1, 418, 342	1, 483, 791	1, 581, 706	1, 598, 572	1, 545, 353	1, 638, 968	1, 579, 064	1, 579, 064	+25.6	1, 257, 478	
(selected represented plants only)	277, 669	306, 151	359, 543	389, 657	397, 355	502, 020	551, 514	506, 071	574, 097	534, 554	533, 332	478, 461	478, 461		(5)	
Stocks on Upper Lake docks:  Lake Superior  Lake Michigan	105, 945 126, 286		90, 418 89, 112	97, 513 69, 050		89, 102 68, 092	88, 194 59, 583	92, 530 74, 892				55, 145 105, 853		-55.7 -29.0	124, 603 149, 124	
Retail stocks—159 selected dealers 4 Producers' stocks 11	417, 988 915, 295		362, 118 655, 560			288, 406 140, 465	284, 585 181, 159	294, 171 289, 023				348, 057 797, 815		-25.6 -37.4		
Prices at mines, average per net ton:  Company Stove	\$6.75	\$6.75	\$6.75	\$6, 50	<b>\$6.75</b>	\$6.75	\$6.75	<b>\$6.</b> 75	\$6.75	\$6.75	\$6.75	\$6.75	<b>\$</b> 6.73	+4.2	\$6,46	
Company Buckwheat No. 1 Wholesale prices:18	\$3.75		<b>\$3.7</b> 5			\$3.75		\$3. 75						+4.2 +2.7	\$3.65	
On tracks, destination: Chestnut Pea Index numbers (1926=100)	\$10. 29 \$8. 89 85. 3	\$10. 29 \$8. 89 85. 3	\$10. 28 \$8. 88 85. 2			\$10.35 \$8.98 85.7	\$10.35 \$8.93 85.7	\$10. 34 \$8, 93 85. 7	\$8.93		\$8.93		\$10.31 \$8.90 85.4	+3.0 +3.6 +3.3	\$10. 01 \$8. 59 82. 7	
Labor conditions: <sup>13</sup> Average weekly earnings	\$26.31	\$33. 23	\$34. 43	<b>\$30.</b> 57	\$35.05	\$40. 25	\$32.09	\$34.00	\$35.40	<b>\$34.3</b> 6	\$35.05	\$36.14	\$33.85	+23.5	\$27.41	
Index of employment (1939 average=100)	97.3	96. 9	96.1	94. 9	95.7	90.4	93.0	92.8	92.5	91.8	91.8	90.9	93.7	-5, 1	98.7	
average=100)	100.7	126. 6	130. 1	114. 2	131. 6	142.9	117. 2	123.0	128.1	123. 4	125. 6	128. 4	124.3	+17.4	105.9	

1 Furnished by Anthracite Institute.
2 Ore and Coal Exchange, Cleveland, Ohio.
3 U. S. Engineer Office, Duluth, Minn.
4 Bituminous Coal Division, U. S. Department of the Interior.
5 Data not available.
6 Furnished by Commonwealth of Massachusetts, Division on the Necessaries of Life. Figures are preliminary.
7 Department of Commerce.
8 Association of American Railroads.
9 Federal Power Commission.
10 National Association of Purchasing Agents.
11 Anthracite Committee. Represents coal in storage closest available date to the end of the month
12 Computed from weekly quotations from trade journals. Figures represent circular prices quoted on white ash by leading anthracite-producing companies.
13 Bureau of Labor Statistics.

The war and anthracite.—Anthracite has contributed to the physical well-being of millions of people who live in the highly populated and industrialized New England and Middle Atlantic States (a large number being employed in vital war industries) and who depend entirely on anthracite for warmth and comfort in the home. In addition to supplying the fuel requirements of those normally using anthracite, the industry was called upon to increase its output substantially to provide heat for thousands of people who had used fuel oil and coke before the war but who were unable to obtain their normal supply on account of shortages resulting from difficulties incurred in transporting oil and the withdrawal of coke from the domestic market because of metallurgical demands. In addition to its use in heating homes, apartments, hotels, hospitals, and public buildings, anthracite is used by railroads, public utilities, and industrial plants; and Army camps are now using substantial quantities for space heating and cooking.

Anthracite aided the war effort not only in the United States but also in Canada, where shortages of gas and oil required increased use of coal. Exports, virtually all of which went to Canada, increased from 2,668,000 net tons in 1940 to 3,380,000 tons in 1941 and totaled 4,439,000 tons in 1942. About 90 percent of the exported coal was

Pea and larger; these sizes are used for comfort heating.

In November 1941 the President by letter requested the Secretary of the Interior to act as Solid Fuels Coordinator for National Defense to handle problems relating to the production, distribution, consumption, and utilization of both anthracite and bituminous coal. Pursuant to this request the Office of Solid Fuels Coordinator for National Defense was established in the Department of the Interior to provide the machinery for carrying out the President's directions. The name of the Office was changed to the Office of Solid Fuels Coordinator for War by direction of the President in May 1942, and in April 1943 the President, in an executive order, abolished the Coordinator's Office and established within the Department of the Interior the Solid Fuels Administration for War with the Secretary of the Interior as Administrator. A Solid Fuels Advisory War Council, organized by the Secretary and composed of representatives of anthracite, bituminous coal, and coke producers, retail dealers, transporters, wholesalers, labor, and the public, met monthly in 1942 to assist and advise the Secretary on matters pertaining to coordination of the Nation's fuel supply to best meet wartime demands.

The needs of the Coordinator's Office for additional basic and current information, both economic and technical, regarding supplies and disposition of the solid fuels necessitated a substantial expansion in the work of the Bureau of Mines regarding these commodities. This applied particularly to coke, production of which could barely meet the needs arising from the great expansion in the metallurgical

industries as a result of the war.

Federal Anthracite Coal Commission.—The Commission's report,¹ containing recommendations for both short-term and long-term measures of improvement, was prepared by the Commission after hearings in the Pennsylvania anthracite regions and study of special reports from Federal, State, and local governmental agencies, civic organizations, and private citizens. The investigation indicated that

<sup>&</sup>lt;sup>1</sup> Economic Conditions in the Anthracite Coal Regions, House Document 709, 77th Congress, 2d Sess. April 21, 1942.

The state of the s

A .

the anthracite area has substantial possibilities for industrial expan-The measures recommended for immediate improvement called attention to the unused manpower with mechanical aptitude and industrious habits and to a reserve of housing facilities, and suggested that war plants, particularly those for the production of aluminum, zinc, castings, armor plate, machine parts, and ammunition, be established in the anthracite regions. The report urged that the industry continue the development of industrial and domestic stokers and automatic heating equipment and investigate ways to expand the industrial uses of anthracite. It was recommended also that current surveys on mine flooding be completed. The measure for long-term improvement included a recommendation that a research station under the direction of the Federal Bureau of Mines be located in the anthracite area to investigate new uses for anthracite, study mining methods, assist in the solution of acid and silt problems in the mine waters, and serve as headquarters for the engineering organization concerned with the industrial development of the area. It was suggested also that an agency be created to study the economic problems arising from the depletion of anthracite reserves and that a survey be made of the anthracite forest region with a view to reforestation.

Anthracite Committee.—Operators whose production represented more than 90 percent of the total output of the industry continued to function under the Voluntary Production-Control Plan for stabilizing the industry. The plan was inaugurated in January 1940 through the cooperation of the Commonwealth of Pennsylvania, the United Mine Workers of America, and the producers and was enacted into the laws of Pennsylvania in 1941. The committee kept in close contact with the illicit mining industry and made every effort to

alleviate this highly unfavorable economic and social problem.

Anthracite Industries, Inc.—One of the immediate objectives of an expanded research program was the development of inexpensive auxiliary equipment to improve the efficiency and convenience of anthracite-burning equipment now in use. The plan also called for cooperation with equipment manufacturers to develop, design, and improve boilers, furnaces, tank heaters, stokers, and other types of equipment for burning anthracite. With new and improved heating equipment, the anthracite industry hopes to take a leading place in the postwar period and to compete successfully with other fuels. This research program is additional to current activities of the organization in assisting the plumbing trade, architects, real estate concerns, and Government agencies interested in the proper equipment for burning anthracite. The anthracite industry's laboratory at Primos, Pa., established standards to guide utilization engineers of the anthracite-producing companies in recommending grate equipment to convert oil-burning boilers and furnaces to anthracite.

Anthracite Institute.—The Anthracite Institute was particularly active in voicing its opposition to the proposed extension of natural-gas pipe lines into the vital eastern markets. In addition, its members represented the producers before various organizations and committees on other problems affecting the anthracite industry. Through its information services it kept the operators informed of pertinent State and Federal legislation, freight rates, Government regulations

and restrictions on the use of oil and gas for fuel, and many other

matters important to the anthracite industry.

Labor.—In December 1942 about 19,000 men went on strike in the Wyoming region in protest against an increase of \$6.00 a year in dues and assessments payable to their union, the United Mine Workers of America, and demanded a wage increase of \$2.00 a day. A general suspension throughout the anthracite region was threatened. Representatives of the producers, the striking miners, and union officials were summoned before the War Labor Board, January 15, 1943, to state fully the reasons for the strike. After hearing the testimony of the interested parties, the Board ordered the miners back to work and suggested that grievances be adjusted through the machinery established in the contract between the producers and the union. Many of the miners refused to obey the order, and on January 19 the War Labor Board turned the case over to the President, who ordered the miners to resume work; within a few days all of them had returned to their jobs.

To meet increased demands for anthracite, the operators and miners agreed to extend the work week from 5 days to 6; the agreement stated that the mine workers were to be paid time and a half and rate and a half for the sixth consecutive day worked in any 1 week. The agreement was contingent on an increase of maximum prices of anthracite by the Office of Price Administration necessary to compensate for increased costs occasioned by payment of overtime for the sixth day. A price increase of approximately 50 cents a ton was authorized, effective January 9, 1943, and within a few weeks the

industry commenced the 6-day week schedule.

Research.—In December 1942 the President approved S. 357, an act passed by the Senate and House of Representatives (56 Stat. 1056), providing for the establishment and operation of a research laboratory in the Pennsylvania anthracite region. Investigations and researches to be conducted through the laboratory facilities will relate to the mining, preparation, and utilization of anthracite; to the development of new uses and markets for anthracite and its products; to safety, health, and sanitation in mining operations; and to any other matters relating to problems of the anthracite industry. The laboratory is to be established, equipped, and maintained by the Secretary of the Interior, acting through the Bureau of Mines. The act authorized appropriation of \$450,000 for the erection and equipment of the necessary buildings and \$175,000 annually for the maintenance and operation of the experiment station.

The cooperative research program sponsored by the Commonwealth of Pennsylvania and the Anthracite Industry at Pennsylvania State College was continued, special attention being paid to the use of anthracite in water-gas generators and in the preparation of activated

carbon.

Research undertaken by Anthracite Industries, Inc., is discussed elsewhere in this chapter under the subheading Anthracite Indus-

tries, Inc.

Competitive fuels in the United States and in principal markets.— More than 95 percent of the anthracite shipped from the mines to points in the United States is destined to the New England States, New York, New Jersey, Pennsylvania, Maryland, Delaware, and the District of Columbia. Data on the consumption of all fuels in these markets are not available; however, the apparent consumption of anthracite, coke, briquets, and heating and range oils, in terms of anthracite, amounted to 84,831,000 net tons in 1941. The sales of heating and range oils in this area in 1941 were the equivalent of 33,284,000 tons of anthracite, and the mine shipments of anthracite to these States totaled 47,466,000 tons. According to the Pennsylvania State Department of Mines, anthracite rail and truck shipments in 1942 to this area totaled 51,546,000 tons. In addition, considerable quantities of "bootleg" or illicit coal were shipped to these The demand for coke for metallurgical use was chiefly responsible for the decline in its consumption for domestic heating from 4,052,000 tons in 1940 to 3,169,000 tons in 1942. Details are shown in table 3.

Table 3.—Apparent consumption of anthracite and selected competitive fuels in the principal anthracite markets, 1939-42

		[Tho	usands o	f net ton	s)		:		
								To	tal
Fuel	New Eng- land	New York	New Jersey	Dela- ware	Mary- land	Penn- syl- vania	District of Co- lumbia	Thou- sands of net tons	Percent of total fuels
Anthracite: All users: 1	11.0								1.0
1939	4, 492	2 16, 716	2 9, 060	259	634	12,077	264	43, 502	58. 2
1940	4, 539	2 16, 249	18,814	304	608	12, 915	289	43, 718	54. 2
1941	5, 540	2 16, 308	2 10, 190	361	681	14, 103	283	47, 466	56.0
1942	5, 844	217, 988	<sup>3</sup> 10, 395	373	835	15, 813	298	51, 546	(3)
	-,					1.		1.11	
1939	298							298	.4
1940	135							135	.2
1941	75							75	.1
1942	140	1						141	(8)
Briquets:						1000			1
Domestic use:					_		1	84	.1
1939	46	23	1		2 2 3	11 10	(5)	91	i
1940	52	26	1	(2)	2	14		95	:i
1941	52	25 26	1	(5) (5) (5)	4	22	(5) (6)	107	(3)
_ 1942	54	20	1	(9)	*	- 22	1 (9)	101	1
Imports: 4 1939	1							1	(6)
1939								-	1
1940									
1941 1942									
Coke:									
Domestic use:					1				k .
1939 7	1,077	1.696	413	5	7	596	2 2 2	3,796	5.0
1940	1, 430	1,564	489	2		537	2	4, 052	5.0
1941	1, 363	1, 350	470	2 1	28 28	474	2	3,688	4.3
1942	1, 252	1,064	408	2	13	428	2	3, 169	(3)
Imports: 4				İ	1		1		
1939	12	19						31	.1
1940	15	58			3			76	.1
1941	65	51			107			223	.3
1942		56						56	(8)
Oil: Heating and range: 8						0.000	458	27, 062	36. 2
1939	10, 787	8, 967	3,770	107	694	2, 279 2, 704	578	32, 543	40.4
1940	13, 027	10, 726	4, 503	120 121	885 963	2, 704	630	33, 284	39. 2
1941	13, 253	10, 940	4,584			(8)	(3)	(3)	(3) 2
1942	(3)	(3)	(3)	(8)	(8)	(9)	(9	(4)	(9)
Total fuel: 9 1939	16, 713	27, 421	13, 244	371	1 337	14, 963	725	74, 774	100.0
	10.713	1 41.441	10.244		1,001				100.0
	10 100	00 802	12 007	198	1 1 59R	I 18 188	I XK9	เพนเหเล	1 1000.01
1940 1940 1941	19, 198 20, 348	28, 623 28, 674	13,807 15,245	426 483	1, 337 1, 526 1, 782	16, 166 17, 384	869 915	80, 615 84, 831	100.0

<sup>&</sup>lt;sup>1</sup> Pennsylvania Department of Mines; illicit coal not included. • remrsyrvants Department of Mines; finicit cost not included.

2 An important but undetermined part of anthracite shown as shipped to New Jersey is reshipped to New York City.

3 Data not yet available.

4 Department of Commerce.

4 Less than 1,000 tons.

5 Less than 1,000 tons.

Less than 0.05 percent.

Estimated upon basis of distribution in 1936.
Converted to coal equivalent upon basis of 4 barrels of fuel oil equaling 1 ton of coal.

<sup>•</sup> Excludes bituminous coal. 556250-43---

In general, the supplies of fuel commonly used for space heating in the United States increased in 1942 over 1941. The increase in anthracite was quite pronounced; coke sales declined, and although data for 1942 on sales of heating and range oils are not available, it is not believed that the use of oil increased appreciably. Details on supplies of various fuels are given in table 4.

Table 4.—Total supplies of fuels commonly used for space heating purposes in the United States, 1924 and 1939-42

[Wherever available, figures represent quantity actually consumed for domestic heating or for space heating offices, apartments, hotels, schools, hospitals, etc. Where such figures are not available but where the fuel is known to be used chiefly for domestic or space heating purposes, total production (or imports) is shown to indicate trend of growthl

	1924	1939	1940	1941	1942
SOLID FUELS (NET TONS)					
Anthracite: Production:					
Shipments of domestic sizes Shipments of Buckwheat No. 1. Shipments of smaller steam sizes 1. Local sales.	56, 576, 296 9, 510, 508 11, 160, 695 3, 043, 939	29, 504, 632 6, 569, 902 9, 917, 748 3, 081, 073	29, 076, 573 6, 771, 387 10, 327, 993 3, 052, 626	30, 912, 649 7, 357, 542 12, 141, 906 3, 695, 125	32, 924, 518 7, 789, 168 13, 196, 015 4, 059, 403
Total commercial production  Exports  Imports for consumption (chiefly from	4, 017, 785	49, 073, 355 2, 590, 000	49, 228, 579 2, 667, 632	54, 107, 222 3, 382, 189	57, 969, 104 4, 438, 589
United Kingdom and U. S. S. R.) Fuel briquets 2 Packaged-fuel production Coke:	580 508	298, 153 880, 981 215, 507	135, 436 1, 027, 585 284, 513	74, 669 1, 258, 129 269, 844	140, 774 1, 644, 755 253, 048
Byproduct sales for domestic use Beehive sales for domestic use Imports for consumption Gas-house-coke sales <sup>3</sup>	139, 886	7, 549, 937 88, 204 141, 911	112, 550	6, 596, 969 85, 990 267, 886	5, 963, 474 98, 220 108, 782
Petroleum-coke production Anthracite and semianthracite production outside of Pennsylvania	761 100	362,000 1,666,400 (4)	1, 526, 600	1, 648, 800	1, 338, 400
Lignite production 5 Bituminous-coal sales for domestic use	2 255 385	3, 042, 537 (6)	2, 939, 201 (6)	2, 775, 832 (6)	(4) (4) (6)
OIL (BARRELS OF 42 GALLONS)					
Oil sales for heating buildings: Range oil. Heating oils: 7 Domestic.	( <del>4</del> )	37, 061, 000	44, 692, 000	46, 110, 000	(4)
Commercial		<b>}</b> 136, 232, 000	160, 379, 000	167, 514, 000	(4)
Liquefied petroleum gases, domestic	(4) (4)	2, 084, 000	3, 191, 000	5, 255, 000	(4)
GAS (MILLION CUBIC FEET)					
Natural-gas consumption for domestic and commercial use §	285, 152	509, 487	578, 290	586, 911	671, 000
Domestic use House heating	(4)	192, 338 55, 561	198, 752 68, 498	198, 700 67, 151	205, 778 79, 600

A considerable part of the smaller steam sizes is used by industries, railroads, and public utilities.

Transportation and distribution of anthracite to principal markets.— According to data compiled from records of the Pennsylvania State Department of Mines, the shipping of anthracite from mines to mar-

<sup>&</sup>lt;sup>2</sup> Production plus imports less exports.

<sup>&</sup>lt;sup>3</sup> Partly estimated

<sup>Partiy estimated.
Data not available.
An estimated one-half is used for domestic purposes.
Exact data not available; estimated between 55 and 77 million tons a year, including lignite. Anthracite and semianthracite outside Pennsylvania shown separately.
Traditional and control of half of proposing buildings.</sup> 

<sup>7</sup> Includes all grades of fuel oil used for heating buildings. 8 Includes gas used for heating offices, hotels, apartments, schools, hospitals, and stores and other large buildings, as well as houses

American Gas Association.

· 大公公公公公公公公

kets by trucks has been increasing continuously since 1936, when truck coal totaled 3,177,656 net tons. In 1941 and 1942 the trucked coal amounted to 7,529,479 and 7,955,738 tons, respectively, and in each year comprised 15 percent of the total shipments of anthracite to destinations in the United States. These tonnage figures represent legitimate coal only and do not include the production from illicit or "bootleg" mines, nearly all of which is trucked to market. Legitimate coal is trucked not only to the ultimate consumer but to many retail dealers within a radius of 150 miles of the anthracite-producing regions.

In 1942 Pennsylvania received 71 percent of the total trucked shipments; New Jersey and New York followed, with 15 and 11 percent, respectively. Before 1941 most of the anthracite moved by truck was shipped during December, January, February, and March;




FIGURE 1.—Anthracite shipped from the Lehigh, Schuylkill, and Wyoming regions, 1850-1942.

however, in 1941 and 1942, because of increased demand for coal, monthly shipments were fairly uniform throughout the year.

Anthracite shipments, by States of destination, for 1940-42 are shown in table 5, and truck movement of anthracite, by months, for

1941 and 1942 is given in table 6.

According to the Commonwealth of Massachusetts, Division on the Necessaries of Life, rail receipts of Pennsylvania anthracite in New England in 1942 totaled 5,393,475 net tons, a gain of 10.8 percent over 1941. Tidewater receipts, including a small amount of imports, were 580,625 net tons in 1942, a decrease of 14.8 percent from 1941. Table 7 gives details of anthracite moved to New England.

Loadings at Lake Erie ports increased from 536,490 tons in 1941 to 575,176 tons in 1942. Receipts on the upper Lake docks declined

from 534,357 tons in 1941 to 443,233 tons in 1942.

Figure 1 illustrates graphically shipments of anthracite from the Lehigh, Schuylkill, and Wyoming regions, 1850–1942.

Table 5.—Shipments of Pennsylvania anthracite, 1940-42, by destinations, in net tons 1

#### [Truck shipments excluded]

Destination	1940	1941	1942
New England States New York New Jersey Pennsylvania Delaware Maryland District of Columbia Virginia Ohio Indiana Illinois Wisconsin Minnesota Michigan Other States	4, 539, 026 15, 477, 318 8, 569, 913 7, 906, 071 197, 456 570, 771 230, 415 106, 713 113, 553 83, 539 265, 424 347, 223 61, 203 203, 299	5, 539, 936 15, 269, 752 8, 858, 652 9, 168, 068 234, 454 627, 936 271, 921 118, 805 119, 710 86, 809 281, 548 320, 500 75, 334 247, 703	5, 843, 834 17, 107, 566 9, 215, 93; 10, 154, 45; 265, 13; 746, 568 283, 761 113, 447 98, 242; 303, 824 394, 328 97, 416 302, 160
Total United States	68, 372 38, 790, 296 2, 312, 531 2, 525 41, 105, 352	52, 223 41, 273, 351 2, 907, 755 13, 061 44, 194, 167	81, 397 45, 134, 848 3, 730, 722 6, 528 48, 872, 098

<sup>&</sup>lt;sup>1</sup> Pennsylvania Department of Mines.

Table 6.—Truck shipments of Pennsylvania anthracite by months in 1942, by States of destination, in net tons 1

Destination	January	February	March	April	Мау	June	July
Pennsylvania:					•		
Within region	395, 055	375, 291	303, 194	298, 950	218, 708	199, 891	174, 498
Outside region	207, 610	203, 113	183, 970	221, 447	221, 909	193, 105	161, 72
New York	99, 601	83, 234	73, 643	77, 861	86, 769	98, 424	66, 55
New Jersey	128, 491	111, 911	100, 519	114, 849	99, 365	123, 196	79, 68
Maryland	4,067	8, 395	4, 343	4,853	9, 301	5, 175	4, 32
Delaware	13,837	11, 266	8, 831	10, 190	9, 970	6, 119	7, 461
District of Columbia	1,435	1,271	1, 161	6	1,507	0,	1, 384
Other States	2, 431	1,940	2, 166	3, 465	2, 146	2, 535	1,789
Total: 1942	852, 527	796, 421	677, 827	731, 621	649, 675	628, 445	497, 416
1941	805, 254	817, 492	808, 805	358, 788	424, 988	621, 654	540, 308
Destination	August	Septem- ber	October	Novem- ber	Decem- ber	Total	Percent of total trucked
Pennsylvania:		-					
Within region	232, 687	243, 142	279,005	269, 074	386, 453	3, 375, 948	42, 4
Outside region	188, 462	185, 438	181, 844	156, 712	177, 148	2, 282, 484	28. 7
New York	61, 996	55, 848	67, 105	56, 093	53, 191	880, 316	11. 1
New Jersey	93, 698	87, 664	87, 486	74, 685	77 764	1, 179, 313	14.8
Maryland	14, 936	7, 415	9, 275	9,011	7, 374	88, 467	1. 1
Delaware	7,461	10,305	8,630	7,459	6,578	108,107	1.4
District of Columbia	1,347	2,414	1, 401	1,006	1, 248	14, 180	1.5
Other States	1, 985	1, 926	2, 094	2, 213	2, 233	26, 923	:8
Total: 1942	602, 572	594, 152	636, 840	576, 253	711, 989	7, 955, 738	100, 0
1941	617, 188	581, 878	608, 238	523, 650	821, 236	7, 529, 479	100.0

<sup>&</sup>lt;sup>1</sup> Compiled from reports of Pennsylvania Department of Mines.

Consumption.—Consumption of anthracite in the United States in 1942, including colliery fuel, amounted to 56,500,000 net tons, an increase of 3,800,000 tons over the calculated consumption in 1941. These figures consider imports and exports of anthracite and changes in producers' stocks but do not allow for changes in stocks held by retail dealers and small consumers, as data on variations of stocks of

these groups were insufficient. The over-all increase in consumption can be attributed largely to increased industrial use and the substitution of anthracite for fuel oil and coke where shortages of these fuels developed in the principal anthracite markets. Electric power utilities and class I railroads consumed 4,009,095 tons of anthracite in

1942 compared with 4,289,936 tons in 1941.

Changes in stocks.—Anthracite producers found it necessary to draw on stocks to meet the 1942 demands. Stocks of 1,273,788 net tons on December 27, 1941, fell to 797,815 tons by January 2, 1943. As the greatest demand was for Egg, Stove, and Nut sizes, the coal in storage on the latter date was largely Pea and smaller, and very little of the domestic sizes was available.

TABLE 7.—Receipts of anthracite in New England, 1917, 1920, 1923, and 1927-42, in thousands of net tons

			Receipts	by tide 1					Total receipts
Year	Maine	New Hamp- shire	Massa- chusetts	Rhode Island	Con- necticut	Total	Receipts by rail 1	Imports 2	of Penn- sylvania anthra- cite *
1917	432	47	2, 222	555	1, 165	4, 421	7, 259	1	11, 679
1920	307	6	2,015	450	743	3, 521	7, 804	1	11, 32
1923	437	27	2,216	511	891	4,082	8, 102	145	12,039
1927	242	33	1, 220	311	615	2, 421	6, 725	106	9.040
928	205	35	1,373	301	528	2, 442	6, 934	369	9,00
929	237	17	1, 227	329	450	2, 260	6, 781	483	8, 558
1930	275	17	1, 236	271	422	2, 221	6, 169	658	7, 73
931	164	18	1,125	282	348	1, 937	5, 125	611	6, 45
932	148	10	1,014	212	275	1, 659	3, 980	574	5,06 4,80
933	195	7	1,027	202	259	1, 690	3, 562	443	4,80
934	168	20	946	190	266	1, 590	4, 382	477	5, 49
935	121	7	802	205	237	1.372	4,030	559	5, 49 4, 84
936	127	14	792	198	267	1,398	3, 889	612	4, 67
937	81	11	604	152	200	1,048	3, 713	395	4, 36
938	93	2	554	137	191	977	3, 491	363	4,10
939	74	3	488	83	227	875	4,027	298	4,60
940	48	4	350	74	172	648	4, 174	135	4,68
941 4	57	. g	348	58	210	682	4,870	75	5, 47
942 4	١ ،		ot availab		1999	581	5, 393	139	5,83

<sup>1</sup> Commonwealth of Massachusetts, Division on the Necessaries of Life.

Stocks held by 159 selected dealers declined from 417,988 net tons in January 1942 to 282,965 tons in September and at the close of the

vear amounted to 348,057 net tons.

Stocks held by electric power utilities and railroads (class I) amounted to 1,774,483 tons on December 31, 1942, compared with 1,496,349 tons on the same date in 1941; stocks held by public utilities increased 26 percent, whereas those of railroads declined 18 percent. Stocks on the upper Lake docks declined from 273,727 tons on December 31, 1941, to 160,998 tons on December 31, 1942.

Illicit coal.—According to the Anthracite Committee, the output of anthracite by the illicit or "bootleg" mining industry amounted to 3,931,000 net tons in 1942, a substantial decrease from the estimated production of 5,000,000 tons in 1941. The decline in output can be attributed largely to the efforts of the committee in arranging for the employment of former "bootleggers" by legitimate companies, as well as to the loss of manpower in the illicit industry because many had taken jobs in near-by war industries. A survey by the committee

<sup>2</sup> Department of Commerce.
3 Total receipts by rail and by tide less imports.
4 Preliminary figures.

in March 1941 indicated that 10,762 men were working 3,006 "bootleg" holes, whereas in May 1942 a comparable survey revealed 7,554 men employed in 2,029 holes. In April 1943 the number of holes had decreased to 1,151 and the men employed totaled 3,100. Sixty-five men were killed in "bootleg" mining in 1940, 54 in 1941, and 49 in 1942.

Trend of employment.—The employment and production trends of

the anthracite industry have been consistently downward from 1926 (when the number of employees totaled 165,386 and the output was 84,437,000 net tons) to 1941. The production curve reversed itself in 1941 and 1942, when the demand for anthracite increased sharply under the stimulus of war; but the number of employees continued to decline until, at the close of 1942, a shortage of several thousand men below the number necessary to meet production requirements existed within the industry. Employment declined from an average of 88,054 men in 1941 to 82,121 in 1942. The induction of men into the armed forces and the loss of others to near-by war industries were largely responsible for the decrease. These figures do not include men working in "bootleg" holes. Data on employment are given in

Trend in prices.—In January 1942 circular f. o. b. mine prices for anthracite were quoted as follows: Broken, Egg, Stove, and Chestnut, \$6.75 a net ton; Pea \$5.25 a ton; Buckwheat, Rice, and Barley, \$3.75, \$2.90, and \$2.15 a ton, respectively. On March 30, 1942 the Office of Price Administration issued Maximum Price Regulation 112, establishing, as maximum prices, those then in effect, which were the same as the January quotations. The regulation also required the granting of seasonal discounts on domestic sizes as follows: April, 50 cents a net ton; May, 40 cents; June, 25 cents; and July, 10 cents. Immediately following issuance of the March 30 price regulation, representatives of the anthracite industry met with price-administration officials on several occasions and urged not only elimination of the discount requirements but also an increase in coal prices. On April 16, 1942, the Price Administrator issued an amendment to Price Regulation 112 which eliminated the seasonal discount and at the same time refused the industry's requests for a 25-cent-per-net-ton price increase for domestic and Pea sizes over the maximum prices established in Price Regulation 112.

Effective January 9, 1943, the Office of Price Administration authorized an increase in maximum prices of anthracite of approximately 50 cents a net ton. The price increase reflected higher production costs incident to extension of the work week from 5 to 6 days, and the payment of time and a half and rate and a half for the sixth consecutive day worked in any 1 week. The new prices, as of January 9, 1943, were \$7.30 per net ton f. o. b. mine for Broken, Egg, Stove, and Chestnut sizes; \$5.75 for Pea; and \$4.20, \$3.35, and \$2.50 for

Buckwheat No. 1, Rice, and Barley sizes, respectively.

Retail prices of anthracite, bituminous coal, coke, and heating oil in selected cities, by months, in 1941 and 1942, are shown in table 8. These prices were compiled from reports of the Bureau of Labor

Statistics, United States Department of Labor.

Sales realization.—The average realization on breaker shipments increased from \$4.59 a net ton in 1941 to \$4.79 in 1942—an increase of 4.4 percent. The average value per net ton of the total anthracite production in 1942 was \$4.50 compared with \$4.26 in 1941.

Table 8.—Retail prices of selected fuels, 1941-42, by cities and months <sup>1</sup> [Coal and coke are per not ton and heating oil per 100 gallons]

	Janua	ry 15	Februs	ry 15	Marc	h 15	Apri	l 15	Маз	15	June	15
City and fuel	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942
Baltimore, Md.:	1				2				146.6			
Anthracite:	\$12, 25	\$12.00	\$11. 25	\$12.00	\$11. 25	\$12.00	\$11, 25	\$11.66	\$11.14	\$12.04	\$10,95	\$12.04
Stove	8. 75	9. 25	8.75	9. 25	8.75	9. 25	8.75	9. 29	8, 66	9. 29	8, 50	9. 29
Buckwheat No. 1 Bituminous coal: Low-Volatile Stove	8. (8)	10. 33	9. 83	10. 33	9. 83	10. 33	9.83	10.33	9.75	10. 33	9.83	10. 33
Bituminous coal: Low-Volatile Stove	9.83		11. 83	12.50	11.83	12.50	12.00	13.00	12.08	12. 52	12.08	12. 52
Coke: Egg	11.83	13.00	11. 00	12, 50	11.00	12.00	12.00	10.00	12.00	12.02	12.00	1
Heating oil:			0.05		0.05	7. 15	6, 47	7.54	6, 97	7, 80	7.06	7.80
Fuel oil No. 2	7. 15	7. 15	6. 95	7. 15	6. 25	7. 15	0.41	7.04	0. 51	1.00	1.00	••••
Fuel oil No. 3												
Boston, Mass.:	,					٠,	. 1			1		
Anthracite:						44 50	10 77	14. 45	13, 75	14, 52	13, 50	14.5
Stove	13.75	14. 50	13. 75	14. 50	13.75	14.50	13. 75			11.02	10.50	11.0
Duckershoot No. 1	1 10 00 1	11.00	10.00	11.00	10.00	11.00	10.00	11.00	10.00	11.02	10. 50	11.0
Bituminous coal: Low-Volatile Stove												14. 2
Coke: Egg.	13. 12	14. 25	13. 32	14. 25	13. 32	14. 25	13. 32	14. 28	13, 35	14.38	13. 28	14. 4
Heating oil:	l l				100				1		0.00	= 0
Fuel oil No. 2	7.00	7. 20	6.80	7. 20	6. 30	7. 20	6.80	7.60	6. 90	7. 78	6. 90	7.8
Fuel oil No. 3	7.00	7. 20	6.80	7. 20	6. 30	7. 20	6.80	7.60	6.90	7.80	6. 90	7.8
Buffalo, N. Y.:		1 1 1 1			100				100			
Anthrocita:			100		1000							
Stove	11.72	12.38	11. 72	12.38	11.72	12.38	11.72	12. 20	11.72	12.44	11.72	12. 4
Buckwheat No. 1	8.48	8. 73	8.48	8, 73	8, 48	8, 73	8.48	8.80	8.48	8.80	8.62	8.7
Bituminous coal; Low-Volatile Stove		00										
Coke: Egg	9.70	10.86	9, 72	10.86	9, 72	10, 98	9.70	10.94	9, 72	10.89	9.72	10. 9
Heating oil:	00	10.00	· · · -	20.00								
Fuel oil No. 2	7, 30	8, 20	7.40	8, 20	7, 20	8, 20	7.40	8, 60	7.60	8, 80	7.70	8.8
Fuel oil No. 3	7. 30	8. 20	7.40	8. 20	7. 20	8. 20	7,40	8,60	7.60	8, 80	7, 70	8.8
	1.00	0.20	1. 10	0.20	20	0.20		0.00				
Chicago, Ill.: <sup>2</sup>	1	100		1.5		1				1		
Anthracite:	14 70	15 55	14, 79	15, 55	14.79	15, 55	14, 79	15, 19	14.77	15.64	14, 77	15. 8
Stove	14.79	15. 55	11. 95	12, 45	11. 95	12.45	11.95	12. 43	11.95	12.48	11. 95	12. 4
Buckwheat No. 1 Bituminous coal: Low-Volatile Stove	11.95	12.45			11. 10	11.87	11. 10	11.59	11. 10	11. 93	11.14	11.
Bituminous coal: Low-Volatile Stove	11.10	11.87	11.10	11.87	12. 52	13.83	12.52	13. 86	12. 50	13.86	12. 55	13.
Coke: Egg	12. 52	13.83	12.52	13.83	12. 52	15.85	12.02	10. 80	12.00	10.00	12.00	10.0
Heating oil:								7.65	7.47	7, 65	7, 47	7.
Fuel oil No. 2	7. 73	7.65	7. 73	7.65	7. 73	7.65	7.47		7. 47	7.65	7. 47	7.
Fuel oil No. 3	7.73	7.65	7. 73	7.65	7.73	7.65	7.47	7.65	7.47	1.00	1.41	
Milwaukee, Wis.:					1	100						
" A 49 166			1					*4.65	10 =^	ایمیر	10 88	14.
Stove	13.70	14. 22	13.70	14. 22	13.70	14. 22	13.70	14. 20	13. 70	14. 24	13. 75	
Buckwheat No. 1	11.00	11. 22	11.00	11. 22	11.00	11. 22	11.00	11. 20	11.02	11. 24	11. 15	11.
Bituminous coal: Low-Volatile Stove	10.90	11.78	10.90	11.78	10.90	11.78	10.90	11.76	10.89	11.76	10.80	11.8
Coke: Egg.	11.48	12.46	11.48	12, 46	11.48	12.46	11.48	12.44	11.48	12.44	11, 48	12.

Table 8.—Retail prices of selected fuels, 1941-42, by cities and months 1—Continued

Other and total	Janus	ary 15	Februs	ary 15	Marc	ch 15	Apri	115	Маз	7 15	Jun	e 15
City and fuel	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942
Milwaukee, Wis.—Continued.												
Heating oil: Fuel oil No. 2	\$7.70	\$7, 70	\$7.70	\$7.70	\$7.70	\$7.70	\$7.70	\$7.70	\$7.70	\$7.70	\$7.70	<b>\$7.70</b>
Fuel oil No. 3	7.70	7.70	7. 70	7.70	7.70	7.70	7. 70	7. 70	7.70	7.70	7.70	\$7. 70 7. 70
New York, N. Y.:3	1										7.70	7.70
Anthracite:	1	**							- 1			
Stove	11.72	12.46	11.72	12.49	11, 72	12.49	11.72	12.47	11.72	12.45	11. 55	12, 42
Buckwheat No. 1	8.38	8, 59	8.38	8.64	8.38	8.64	8. 38	8. 62	8. 38	8.60	8. 47	8. 55
Bituminous coal: Low-Volatile Stove												
Coke: Egg	12. 27	13. 05	12. 27	13.05	12. 27	13. 05	12. 27	12, 58	11.62	13. 05	11.98	13. 16
Heating oil: Fuel oil No. 2	1 000				0.00			1				
Fuel oil No. 2	6. 94 6. 94	7. 27 7. 27	6. 45	7. 27	6. 28 6. 32	7. 27	6. 43	7.68	6.83	7.88	6.89	7.88
Philadelphia, Pa.:	0.94	1.21	6. 45	7. 27	0. 32	7. 27	6.43	7.68	6.83	7.88	6. 91	7.88
Anthracite:				1 1		100						
Stove	10, 72	11.67	10.69	11.67	10, 72	11.67	10.72	11. 25	10.62	11.67	10.60	11.69
Buckwheat No. 1	7.80	8. 50	7.80	8.50	7, 80	8, 50	7.80	8, 50	7.80	8.50	7. 82	8, 52
Bituminous coal: Low-Volatile Stove		3.55		0.00		0.00		0.00		0.00	1.02	0.04
Coke: Egg		11.75	10.75	11.75	10.75	11.75	10.75	11.81	10.75	11.75	10.75	11.75
Heating oil:												22
Fuel oil No. 2	6.75	7.18	6.73	7. 18	6.00	7.18	6.41	7. 56	6.98	7.76	7.00	7. 76
Fuel oil No. 3.	6.75	7.17	6.72	7.17	6.00	7. 17	6.40	7. 56	6. 98	7.76	7.00	7. 76
Portland, Maine:		: (			3 B				1. 1. 1.			
Anthracite:	1 40 40 1	44.50	40 70			4						
Stove	13.50	14.50	13. 50	14.50	13, 50	14.50	13.50	14.50	13. 50	14. 50	13. 50	14. 50
Buckwheat No. 1	10.50	10.75	10. 50	10.75	10.50	10.75	10.50	10.75	10.50	10.75	10.50	10. 75
Coke: Egg.		13. 25	12.50	13. 25	12, 50	13. 25	12.50	13. 25	12.50	12.05		
Heating oil:	1	15. 20	12.00	15. 25	12, 50	15. 25	12. 50	13. 20	12. 00	13. 25	12. 50	13, 25
Fuel oil No. 2	7.00	7, 20	6, 83	7, 20	6, 30	7, 20	6.80	7, 60	6, 90	7.77	6, 90	7.77
Fuel oil No. 3	1.00	1.20	0.00	7.20	0.50	1.20	0.00	7.00	0. 80	1.11	0. 90	1.11
Washington, D. C.;4												
Anthracite:	1								- Later Late	te est fil		
Stove	12.95	13.86	12.95	13.70	12.95	13.70	12.95	13. 26	12.95	13, 76	12.84	13, 76
Buckwheat No. 1  Bituminous coal: Low-Volatile Stove	9. 60	10.12	9.60	10.00	9, 60	10.00	9.60	10.04	9.60	10.06	9.63	10.06
Bituminous coal: Low-Volatile Stove	10.86	11.50	10.86	11.38	10.86	11.38	10.86	11. 22	10.86	11.38	10.70	11. 38
Coke: Egg	11.00	12.54	11.00	12.58	11.00	12.58	11.00	12.61	11.00	12.62	12.00	12. 55
Heating oil:										+ + <u>1</u>	1	
Fuel oil No. 2	7.38	7.60	7. 20	7. 60	6. 75	7.60	6.75	8.00	7. 25	8. 20	7. 25	8. 20
Fuel oil No. 3	1											5.00

c	-
ĭ	3

	September 15		October 15		November 15		December 15	
1942 1941	1942	1941	1942	1941	1942	1941	1942	
\$12.04   \$12.00		\$12.00	\$12.04	\$12.00	\$12.04	\$12.00	\$12.08	
9. 29 9. 25		9. 25	9. 29	9. 25	9. 29	9. 25	9.3	
10.33 10.33		10. 33	10. 33	10.33	10.43	10. 33	10.4	
12. 52   12. 08	08 12.52	12. 50	12. 52	12. 50	12. 52	12. 50	12. 5	
8, 55 7, 15			0 =0					
8. 55 7. 15	5 8.55	7.15	8. 70	7.15	8.70	7.15	8.7	
		· 1						
14.58 14.50	60 14.58	14. 50	14. 58	14.50	14. 58	14, 50	14. 5	
11.08 11.00		11.00	11.08	11.00	11.08	11.00	11.0	
11.00	N 11.00	11.00	11.00	11.00	11.08	11.00	11.0	
14. 25 13. 95	14. 25	14. 19	14, 25	14. 25	14. 25	14. 25	14. 2	
11.20 10.00	70 11.20	14.10	14.20	14.20	14. 20	14. 20	14. 2	
8.79 7.20	20 8.70	7, 20	8, 70	7, 20	8, 70	7, 20	8.7	
8. 92 7. 20	8.70	7. 20	8.70	7. 20	8. 70	7. 20	8. 7	
5.12		20	٠٠		0.10	20	0. 1	
1					J	1 2		
12. 42 12. 30	30 12.42	12.38	12, 42	12, 38	12, 42	12.38	12.4	
8.77 8.72	2 8.77	8. 73	8.77	8. 73	8. 77	8. 73	8. 7	
10. 97   10. 52	2 10.97	10.71	10.97	10.81	10.97	10.81	10. 9	
	1 1							
9.70 8.00		8. 20₹	9.70	8. 27	9.70	8. 23	9.7	
9.70 8.00	0 9.70	8. 20	9.70	8. 27	9. 70	8. 23	9.7	
			4.1					
15. 58 15. 32		15. 47	15. 58	15. 53	15. 58	15. 53	15. 5	
12. 45 12. 32		12.40	12. 45	12.42	12.45	12.42	12.4	
11. 90 11. 67		11.81	11.90	11.85	11.90	11.85	11.9	
13. 81 13. 46	16 13.84	13.62	13.84	13. 78	13.84	13. 81	13.8	
7. 65 7. 61		7, 65	- 05		- 0-			
7. 65 7. 56		7.65	7. 65 7. 65	7. 65 7. 65	7.65	7.65	7.6	
1.00	1.00	7.00	7.00	7.00	7.65	7.65	7. 6	
14. 25 14. 22	2 14.25	14.22	14, 25	14. 22	14, 25	14, 22	14. 2	
11. 25   11. 22		11. 22	11. 25	11. 22	11. 25	11. 22	14. 2	
							11.2	
		19.46					12.4	
11.00	12. 44	12. 10	14. 11	12. 40	14.44	12.40	12.4	
7 70 7 70	7 70	7 70	7 70	7 70	7 70	7 70	7.7	
7 70 7 70	7 70				7.70		7.7	
	12. 44 11. 9 7. 70 7. 7	12. 44 11. 96 12. 44 7. 70 7. 70 7. 70	12.44         11.96         12.44         12.46           7.70         7.70         7.70         7.70	12. 44   11. 96   12. 44   12. 46   12. 44   7. 70   7. 70   7. 70   7. 70   7. 70	12.44     11.96     12.44     12.46     12.46     12.44     12.46       7.70     7.70     7.70     7.70     7.70     7.70	12. 44   11. 96   12. 44   12. 46   12. 44   12. 46   12. 44   12. 46   12. 47   12. 48   12.	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	

Table 8.—Retail prices of selected fuels, 1941-42, by cities and months 1—Continued

	July	y 15	Augu	ıst 15	Septen	aber 15	Octob	er 15	Novem	iber 15	Decem	ber 15
City and fuel	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942
New York, N. Y.:3												
Anthracite:		410.10	410.01		010.44	010.45	410.47	010 AF	410.05	010.45	610.05	\$12, 46
Stove.	\$11. 92 8. 56	\$12. 42 8. 55	\$12. 21 8. 59	\$12.45 8.55	\$12.44 8.57	\$12.45 8.55	\$12.47 8.57	\$12.45 8.55	\$12.35 8.48	\$12.45 8.55	\$12.35 8.48	\$12.40 8.56
Buckwheat No. 1 Bituminous coal: Low-Volatile Stove	- 8.00	-8. 99	ი. მმ	0.00	0.07	0.00	0.01	8. 99	0.40	0.00	0.40	<b>6.</b> 50
Coke: Egg	12.64	13.16	12.95	13. 16	13. 01	13. 16	13, 12	13. 16	12.99	13.16	12.99	13.16
Heating oil:	12.01	10.10	12.00	10.10	10.01	10.10	10.12	10.10	A	-00		
Fuel oil No. 2		9.90	7. 20	8.79	7. 22	8. 79	7. 30	8.79	7. 27	8.79	7. 27	8.79
Fuel oil No. 3	6.91	9.90	7. 22	8.79	7. 22	8. 79	7. 29	8.79	7. 27	8. 79	7. 27	8.79
Philadelphia, Pa.:										i		
Anthracite:					** **		** 04		04			11 50
Stove	10.82	11.69	11.28	11. 69 8. 53	11. 58 8. 42	11.69 8.53	11.64	11. 70 8. 53	11. 64 8. 50	11.70 8.53	11. 64 8. 50	11. 70 8. 53
Buckwheat No. 1 Bituminous coal: Low-Volatile Stove	7.98	8. 53	8.17	8. 53	8.42	8. 53	8. 50	8.03	8. 50	8.00	8. 50	8. 03
Coke: Egg	11.10	11. 75	11. 44	11.75	11.50	11.75	11. 56	11.75	11. 75	11.75	11.75	11. 75
TT ( for a 1 - 1) .		11.70	11. 11	11.10	11.00	11.70	11.00	11.70	11.10	110	11.10	11.70
Fuel oil No. 2	6, 98	9, 58	6, 98	8, 59	7.18	8, 59	7.18	8. 59	7, 18	8, 56	7.18	8, 56
Fuel oil No. 3	6.98	9, 56	6.98	8, 58	7.17	8. 58	7.17	8, 58	7.17	8, 55	7.17	8. 55
Portiand, Maine:		7.77										
Anthracite:		25		100	7 1							
Stove	14.00	14. 50	14.00	14.50	14. 50	14. 50	14.50	14. 50	14. 50	14. 50	14. 50	14. 50
Buckwheat No. 1  Bituminous coal: Low-Volatile Stove	10.75	10.75	10.75	10.75	10.75	10.75	. 10. 75	10.75	10.75	10.75	10.75	10.75
Bituminous coal: Low-Volatile Stove	12. 50		12. 50	13. 25	12, 50	13. 25	13. 25	13. 25	13. 25	13. 25	13. 25	13. 25
Coke: EggHeating oil:	. 12.50	13. 25	12. 50	13. 25	1,2, 50	13. 25	13. 23	13. 23	13. 23	15. 20	15. 20	10. 20
Fuel oil No. 2	6.90	9, 80	7.15	8, 70	7, 20	8, 70	7, 20	8, 70	7. 20	8, 70	7. 20	8, 70
Fuel oil No. 3	. 0.30	9.00	1.10	3.10	1.20	0.10	1.20	0.10	1.20	0.10	1.20	0.10
Washington, D. C.:4												
Anthracite:												
Stove Buckwheat No. 1	13.12	13.76	13. 42	13.76	13. 45	13. 76	13.70	13.76	13.70	13.76	13.70	13. 76
Buckwheat No. 1	9. 76	10.06	9.89	10.06	9. 90	10.06	10.00	10.06	10.00	10.06	10.00	10.06
Bituminous coal: Low-Volatile Stove	. 11.00	11.38	11.30	11.41	11.32	11.43	11.38	11.44	11.38	11. 44	11.38	11. 44
Coke: Egg	12.00	12. 55	12.36	12.55	12.42	12. 55	12. 50	12. 55	12. 50	12. 55	12.50	12. 55
Heating oil: Fuel oil No. 2	7 05	0.01	7 01	0.10	7 70	9, 10	7.70	9. 10	7, 70	9, 10	7, 60	9, 10
Fuel oil No. 2	7, 25	9. 91	7. 31	9.10	7. 70	9. 10	7.70	9. 10	7.70	9, 10	7.00	9. 10
Fuel oil No. 3	-											

Compiled from reports of the Bureau of Labor Statistics, Department of Labor. 1942 data are preliminary. 1941 coke and oil figures are preliminary.
 Includes 3-percent sales tax in 1941 through June and 2-percent July 1941 through December 1942.
 Includes 2-percent sales tax.
 Prices of coal per ton of 2,240 pounds.

Freight rates.—A number of changes affecting the freight-rate structure for anthracite were authorized by the Interstate Commerce Commission in 1942. The so-called motor-compelled rates, which were originally established to compete with the trucking of anthracite, were to expire on December 20, 1942, but were extended to June 20, Early in 1942 the railroads were authorized to increase freight rates on all commodities, the specific increases on coal being 3 cents per net ton for rates of \$1.00 or less and 5 cents per net ton for those over \$1.00 a ton. The authorization was issued by the Interstate Commerce Commission on March 2, 1942, and the charges were made effective not later than May 15, 1942. The increases as approved were for the war period and 6 months thereafter. Late in 1942 the Office of Price Administration filed a petition with the Commission asking for reopening of the case and reconsideration with a view to discontinuation of the increases allowed, pointing out that the increases were granted primarily to produce additional revenue for the railroads but that earnings would now be exceedingly favorable if the adjustments granted had not been in effect. In April 1943 the Commission ordered cancellation of the increases, effective May 15, 1943, for a temporary period ending December 31, 1943, during which time further consideration will be given to the comprehensive record along with the developments during the interim. Late in 1942 an examiner of the Interstate Commerce Commission recommended a reduction of 46 cents a gross ton in anthracite freight rates from the mines to New York tidewater piers. The recommendation was argued by interested parties before the Commission in April 1943, and the final decision of that body is pending. The revenue act of 1942 imposed a tax on the transportation of anthracite amounting to 4 cents a net ton, effective December 1, 1942.

Imports and exports.—Exports of anthracite increased from 2,667,632 net tons in 1940 to 3,380,189 tons in 1941 and reached a total of 4,438,589 tons in 1942—the greatest tonnage exported since 1923, when shipments were 5,090,138 tons. Almost all exports were destined to Canada, where a shortage of coke and restrictions on the use of heating oils and gas created a heavy demand for Pennsylvania The shipments to Canada were largely domestic sizes, and the industry hopes that gains in this market will be retained after Exports were valued at \$21,210,499 in 1940, \$27,691,017 in 1941, and \$38,286,755 in 1942. Anthracite imports declined from 135,436 tons in 1940 to 74,669 in 1941 and then increased to 140,774

(See tables 30 to 32.) tons in 1942.

Mechanical stokers and oil burners.—Government restrictions on the manufacture and installation of stokers and oil burners were largely responsible for the sharply reduced sales of this equipment in 1942. According to the Bureau of the Census, United States Department of Commerce, factory sales of mechanical stokers (class 1) for burning anthracite decreased from 17,110 units in 1941 to 11,562 in 1942. Sales of class 2 stokers (capacity 61 to 100 pounds of coal per hour) declined from 599 in 1941 to 356 in 1942.

Shipments of oil burners fell from 303,869 units in 1941 to 131,031 These figures do not include burners used in water heaters, stoves, ranges, and space heaters, but do include both domestic and foreign shipments.

## SOURCES AND ACKNOWLEDGMENTS

Annual statistics of the Pennsylvania anthracite industry are prepared, for the most part, from reports received direct from the producers and shippers of anthracite, as a result of a canvass conducted by mail. More than 95 percent of the tonnage is reported in this manner, and the remainder is obtained personally by a representative of the Bureau of Mines or from reliable collateral evidence. The information as furnished by the producers is voluntary and is held confidential, as is customary with the statistical services of the Bureau of Mines.

In compiling available information, pertinent statistics prepared by the Anthracite Committee, the Anthracite Institute, the American Association of Railroads, and the Pennsylvania Department of Mines have been used to advantage. The Bureau of Mines gratefully acknowledges the cooperation of these and others from whom information has been received.

# PRODUCTION

Production of Pennsylvania anthracite in 1942 totaled 60,328,000 net tons—an increase of 7 percent over the output of 56,368,000 tons in 1941. These statistics include deep-mined and strip-pit production, culm-bank coal, anthracite purchased by the legitimate industry from "bootleggers," and river or dredge coal, which is recovered from the rivers and creeks draining the anthracite fields. Also included is a small amount of semianthracite produced in Sullivan County (48,213 net tons in 1942).

See tables 9 to 18 for production and shipments by regions, fields, and counties.

Before 1930 anthracite was mined only by companies who owned or leased the coal lands. During the depression years of the early 1930's unemployed miners dug anthracite from lands of the operating companies without the permission of the owners or lessees, and trucks transported the coal to distant cities where it was sold in competition with the legitimate product. In 1941 the illicit coal tonnage was estimated at about 5,000,000 net tons, and in 1942 the Anthracite Committee estimated "bootleg" production at 3,931,000 tons. Before 1941 "bootleg" coal was not included in the production statistics of the Pennsylvania anthracite industry by the Bureau of Mines. 1941, however, legitimate operators lawfully purchased run-of-mine coal from "bootleggers" and shipped 1,902,481 tons of the prepared product to market, and in 1942 the purchases totaled 2,616,839 tons. It would be impractical to segregate this purchased "bootleg" coal from the output of the legitimate industry, and it is therefore included in the various production tables in the Minerals Yearbook chapters on Pennsylvania anthracite for 1941 and 1942. For this reason, the production statistics for those years are not exactly comparable with previous years. No attempt has been made to include in the statistics

"bootleg" coal other than that purchased by legitimate operators. To compute the output per man per day for the anthracite industry in 1941 and 1942, it was necessary to deduct the "bootleg" purchases from the total tonnage shipped by the legitimate industry since adequate data on man-hours required to produce the bootleg tonnage

are not available. Details of this procedure are discussed in this

chapter under Labor Statistics.

Weeks and months.—Tables 9 and 10 summarize the statistics of weekly and monthly production of anthracite. Statistics of current output are estimated from records of car loadings and other pertinent data. The weekly and monthly figures in tables 9 and 10 have been adjusted to the annual total ascertained by direct canvass of the operators.

Table 9.—Estimated weekly production of Pennsylvania anthracite in 1942, in net tons

Week ended—	Net tons	Week ended—	Net tons
Jan. 3	832,000	July 18 25	1, 237, 000
17 24 31	1, 273, 000 1, 103, 000	Aug. 1	1, 234, 000 1, 269, 000
Feb. 7	1, 175, 000 1, 166, 000	22	1, 244, 000 1, 248, 000
28 Mar. 7	1, 186,000 1, 182,000	12 19 26	1, 265, 000 1, 284, 000
21 28 Apr. 4	1, 165, 000 885, 000	Oct. 3	1, 166, 000 1, 147, 000
18 25 May 2	1, 326, 000	24	1,091,000 1,181,000
9 16 23	1, 274, 000 1, 270, 000	21 28 Dec. 5	1, 165, 000 1, 163, 000
30 June 6	818,000 1,048,000 1,186,000	12 19 26	1, 108, 000 1, 121, 000 779, 000
20 27 July 4	1, 246, 000	Calendar year	

<sup>&</sup>lt;sup>1</sup> Figures represent output of working days in that part of week included in the calendar year 1942. Preliminary production for week of January 2, 1943, was 796,000 tons. Revised total for week of January 3, 1942, was 752,000 tons.

Table 10.—Estimated monthly production of Pennsylvania anthracite, 1935-42, in thousands of net tons 1

Month	1935	1936	1937	1938	1939	1940	1941	1942 2
January February March April May June July August September October November	5, 790 4, 652 3, 228 4, 763 5, 118 5, 724 3, 502 3, 073 4, 113 4, 132 3, 432	5, 315 6, 952 3, 051 4, 757 5, 104 4, 292 3, 912 3, 492 3, 861 4, 593 4, 320	4, 236 3, 671 4, 795 6, 779 4, 361 4, 635 2, 748 2, 903 3, 682 4, 848 4, 439	4, 978 3, 646 4, 257 3, 149 4, 400 4, 450 2, 580 2, 735 3, 388 4, 180 3, 803	5, 019 4, 169 3, 652 5, 367 5, 141 3, 577 2, 951 3, 883 4, 984 4, 985 3, 989	5, 783 3, 648 3, 881 3, 853 4, 070 4, 492 4, 534 3, 883 4, 172 4, 355 3, 980	5, 162 4, 596 4, 765 3, 317 4, 001 5, 072 4, 855 5, 441 5, 334 5, 580 3, 974	4, 566 4, 801 5, 116 5, 184 4, 873 5, 155 5, 377 5, 212 5, 452 5, 133 4, 824
December	4, 632	4, 931	4,759	4, 533	3, 914	4, 834	4, 271	4, 63
	52, 159	54, 580	51,856	46, 099	51, 487	51, 485	56, 368	60, 32

<sup>&</sup>lt;sup>1</sup> Production is estimated from weekly carloadings as reported by the Association of American Railroads and includes mine fuel, coal sold locally, and dredge coal. Monthly statistics from 1905 to 1925 will be found in Mineral Resources, 1925, pt. II, pp. 427-428, and from 1925 to 1930 in Mineral Resources, 1930, pt. II, p. 741.

<sup>2</sup> Includes some "bootleg" coal purchased by legitimate operators and prepared at their breakers.

Table 11.—Pennsylvania anthracite shipped, sold locally, and used as colliery fuel in 1942, by regions

Postor	Ship	ments	Loca	l sales	Collie	ry fuel	То	tal
Region	Net tons	Value 1	Net tons	Value	Net tons	Value	Net tons	Value 1
Lehigh: Breakers Washeries Dredges	8, 822, 265 244, 364 9, 042	\$41, 540, 000 806, 000 10, 000	457, 773 27, 849 343	\$2, 470, 000 79, 000 1, 000	364, 241 2, 000	\$799, 000 5, 000	9, 644, 279 274, 213 9, 385	\$44, 809, 000 890, 000 11, 000
Total Lehigh	9, 075, 671	42, 356, 000	485, 965	2, 550, 000	366, 241	804, 000	9, 927, 877	45, 710, 000
Schuylkill: Breakers. Washeries. Dredges	16, 935, 772 1, 580, 033 744, 910	73, 714, 000 3, 974, 000 874, 000	724, 338 36, 792 503, 061	2, 808, 000 75, 000 702, 000	333, 832 27, 516 3, 610	611, 000 57, 000 4, 000	17, 993, 942 1, 644, 341 1, 251, 581	77, 133, 000 4, 106, 000 1, 580, 000
Total Schuylkill	19, 260, 715	78, 562, 000	1, 264, 191	3, 585, 000	364, 958	672, 000	20, 889, 864	82, 819, 000
Wyoming: Breakers Washeries Dredges	25, 390, 166 133, 529 24, 067	129, 724, 000 211, 000 34, 000	2, 287, 502 125	10, 802, 000 1, 000	1, 591, 803 34, 583	2, 164, 000 61, 000	29, 269, 471 168, 237 24, 067	142, 690, 000 273, 000 34, 000
Total Wyoming	25, 547, 762	129, 969, 000	2, 287, 627	10, 803, 000	1, 626, 386	2, 225, 000	29, 461, 775	142, 997, 000
Total, excluding Sullivan County: Breakers. Washeries. Dredges.	51, 148, 203 1, 957, 926 778, 019	244, 978, 000 4, 991, 000 918, 000	3, 469, 613 64, 766 503, 404	16, 080, 000 155, 000 703, 000	2, 289, 876 64, 099 3, 610	3, 574, 000 123, 000 4, 000	56, 907, 692 2, 086, 791 1, 285, 033	264, 632, 000 5, 269, 000 1, 625, 000
Total	53, 884, 148 25, 553	250, 887, 000 78, 000	4, 037, 783 21, 620	16, 938, 000 68, 000	2, 357, 585 1, 040	3, 701, 000 1, 000	60, 279, 516 48, 213	271, 526, 000 147, 000
Grand total: 1942	53, 909, 701 50, 412, 097 +6. 9	250, 965, 000 222, 173, 000 +13. 0	4, 059, 403 3, 695, 125 +9. 9	17, 006, 000 14, 825, 000 +14, 7	2, 358, 625 2, 261, 045 +4. 3	3, 702, 000 3, 277, 000 +13. 0	60, 327, 729 56, 368, 267 +7. 0	271, 673, 000 240, 275, 000 +13. 1

<sup>&</sup>lt;sup>1</sup> Value given is value at which coal left possession of producing company; does not include margins of separately incorporated sales companies.

<sup>2</sup> For purposes of historical comparison and statistical convenience, the mines of Sullivan County are grouped with the Pennsylvania anthracite region, although the product is classified as semianthracite according to the American Society for Testing Materials Tentative Standard.

Small mines and intercompany sales.—Many small, independently owned mines produce run-of-mine anthracite, which is shipped by rail or truck to breaker companies for preparation and transportation to market. Also, a number of the larger companies have built central cleaning plants for preparing run-of-mine coal from their own mines. This tendency within the industry of transferring run-of-mine coal from one company to another and the trend toward central preparation plants have increased the complexity of compiling the statistics; however, every effort has been made to avoid any duplication of The men employed in producing run-of-mine coal have been included in the labor statistics and are an appreciable part of the total number of employees engaged in production work. This reference to independently owned mines concerns legitimate operations only and should not be confused with illicit or "bootleg" mines, for which complete employment data are not available.

Regions, fields, and counties.—The main anthracite region covers an elongated area of about 480 square miles in eastern Pennsylvania, with its longer axis running northeast and southwest. The area is divided into three regions—Lehigh, Schuylkill, and Wyoming. classification is generally used by the trade, and it is also followed in the district organization of the United Mine Workers of America, in which district 1 corresponds to the Wyoming region, district 7 to the Lehigh region, and district 9 to the Schuylkill region. The Wyoming region covers a single geologic anthracite basin and is about 54 miles long by 6 miles wide at its widest point; the Lehigh region comprises the anthracite lands tributary to the Lehigh River that forms its eastern boundary and contains the Eastern Middle field and the section of the Southern field lying east of Tamaqua; and the Schuylkill region consists of the Western Middle field and the section of the Southern field lying west of Tamaqua.

The area is divided also into four fields, using the grouping of the anthracite geologic basins as a framework, as follows: The Northern field, which is the same as the Wyoming region; the Eastern Middle or Lehigh field, which consists of a group of at least 10 small basins; the Western Middle field, a single basin about 36 miles long by 4½ miles at its widest point; and the Southern field, also a single basin, about 54 miles long by 6 miles at its widest point, which breaks into a

long "fishtail" toward its western ends.

Table 12.—Pennsylvania anthracite produced, 1938-42, by fields, in net tons [The figures of breaker product include a certain quantity of culm-bank coal, which amounted to 2,648,273 tons in 1942. Data for 1913-25 will be found in Mineral Resources, 1925, pt. II, p. 517, and for 1919-30 in Mineral Resources, 1930, pt. II, p. 747]

Field	1938	1939	1940	1941	1942
Eastern Middle: Breakers Washeries Dredges	5, 217, 169	1 5, 444, 335 (1)	1 5, 104, 708 (¹)	5, 066, 892 217, 642 5, 032	5, 717, 908 259, 378
Total Eastern Middle	5, 217, 169	5, 444, 335	5, 104, 708	5, 289, 566	5, 977, 286
Western Middle: Breakers Washeries Dredges	8, 877, 485 940, 938 223, 961	9, 242, 223 906, 992 253, 819	10, 168, 142 734, 541 447, 760	11, 531, 105 946, 794 531, 129	13, 122, 774 333, 089 466, 339
Total Western Middle	10,042,384	10, 403, 034	11,350,443	13, 009, 028	13, 922, 202
Southern: Breakers Washeries Dredges	5, 447, 804 625, 335 317, 572	6, 196, 051 855, 659 432, 974	6, 615, 347 812, 162 492, 684	7, 445, 528 1, 116, 438 975, 457	8, 797, 539 1, 326, 087 794, 627
Total Southern	6, 390, 711	7, 484, 684	7, 920, 193	9, 537, 423	10, 918, 253

<sup>1</sup> Small quantity of washery coal included with breaker.

TABLE 12.—Pennsylvania anthracite produced, 1938-42, by fields, in net tons-Con.

Field	1938	1939	1940	1941	1942
Northern: Breakers Washeries Dredges	24, 059, 598	27, 806, 467	26, 571, 383	28, 097, 833	29, 269, 471
	310, 491	295, 103	484, 569	391, 452	168, 237
	29, 491	17, 067	2, 500	5, 945	24, 067
Total Northern	24, 399, 580	28, 118, 637	27, 058, 452	28, 495, 230	29, 461, 775
Total, excluding Sullivan County:  Breakers Washeries Dredges	43, 602, 056	1 48, 689, 076	1 48, 459, 580	52, 141, 358	56, 907, 692
	1, 876, 764	1 2, 057, 754	1 2, 031, 272	2, 672, 326	2, 086, 791
	571, 024	703, 860	942, 944	1, 517, 563	1, 285, 033
TotalSullivan County: Breakers	46, 049, 844	51, 450, 690	51, 433, 796	56, 331, 247	60, 279, 516
	49, 183	36, 687	50, 844	37, 020	48, 213
Grand total	46, 099, 027	51, 487, 377	51, 484, 640	56, 368, 267	60, 327, 729

<sup>1</sup> Small quantity of washery coal included with breaker.

Table 13.—Pennsylvania anthracite produced in 1942, by counties

County	Total sl	hipments	Sold to 1	ocal trade	Used for	r power	Total p	roduction
	Net tons	Value 1	Net tons	Value	Net tons	Value	Net tons	Value 1
Carbon Columbia Dauphin Lackawanna Luzerne Northumberland	129, 214 42, 296 6, 877, 722	107,000 33,989,000 114,426,000	29, 361 290, 393 862, 591 1, 636, 016	451,000 4,244,000	6, 853 1, 720 446, 477 1, 364, 214	24,000 2,000 681,000 1,964,000	165, 428 334, 409 8, 186, 790	560,000
Schuylkill Sullivan Snyder, Susquehanna,	15, 458, 439 25, 553	62, 922, 000 78, 000	452, 988 21, 620	2, 002, 000 68, 000	314, 151 1, 040	629, 000 1, 000	16, 225, 578 48, 213	65, 553, 000
and Wayne	176, 645 35, 836					61,000	227, 649 201, 845	
						3, 702, 000		271, 673, 000

 <sup>1</sup> Value given for shipments is value at which coal left possession of producing company and does not include margins of separately incorporated sales companies.
 2 Counties producing dredge coal only.

Table 14.—Pennsylvania anthracite produced in 1942, classified as fresh-mined, culm-bank, and river coal and as breaker, washery, and dredge product, by regions, in net tons

		From mine	<b>S</b> .			
Region and type of plant	Under	ground		From culm	From river	Total
	Mechan- ically loaded	Hand loaded	Strip pits	banks	dredging	
Lehigh: Breakers	815, 954	6, 095, 234	2, 261, 370	471, 721 274, 213	9,385	9, 644, 279 274, 213 9, 385
Total Lehigh	815, 954	6,095,234	2, 261, 370	745, 934	9, 385	9, 927, 877
Schuylkill: Breakers Washeries Dredges	1,759,818	9, 178, 146	5, 170, 562	1, 885, 416 1, 644, 341	1, 251, 581	17, 993, 942 1, 644, 341 1, 251, 581
Total Schuylkill	1,759,818	9, 178, 146	5, 170, 562	3, 529, 757	1, 251, 581	20, 889, 864
Wyoming: Breakers	12, 165, 687	15, 173, 647	1, 639, 001	291, 136 168, 237	24, 067	29, 269, 471 168, 237 24, 067
Total Wyoming	12, 165, 687	15, 173, 647	1, 639, 001	459, 373	24,067	29, 461, 775
Total, excluding Sullivan County: Breakers Washeries Dredges	14, 741, 459	30, 447, 027	9, 070, 933	2, 648, 273 2, 086, 791	1, 285, 033	56, 907, 692 2, 086, 791 1, 285, 033
TotalSullivan County: Breakers	14, 741, 459	30, 447, 027 48, 213	9,070,933	4,735,064	1, 285, 033	60, 279, 516 48, 213
Grand total	14, 741, 459	30, 495, 240	9,070,933	4, 735, 064	1, 285, 033	60, 327, 729

Table 15.—Pennsylvania anthracite produced in 1942, classified as fresh-mined, culm-bank, and river coal and as breaker, washery, and dredge product, by fields, in net tons

		From mine	3			
Field and type of plant	Under	ground		From culm	From river dredg-	Total
	Mechani- cally loaded	Hand loaded	Strip pits	banks	ing	
Eastern Middle: Breakers	815, 954	3, 342, 837	1,138,967	420, 150 259, 378		5, 717, 908 259, 378
Total Eastern Middle	815, 954	3, 342, 837	1, 138, 967	679, 528		5, 977, 286
Western Middle: Breakers Washeries Dredges	1, 706, 354	6, 979, 239	3, 023, 783	1, 413, 398 333, 089	466, 339	13, 122, 774 333, 089 466, 339
Total Western Middle	1, 706, 354	6, 979, 239	3, 023, 783	1, 746, 487	466, 339	13, 922, 202
Southern: BreakersWasheriesDredges	53, 464	4, 951, 304	3, 269, 182	523, 589 1, 326, 087	794, 627	8, 797, 539 1, 326, 087 794, 627
Total Southern	53, 464	4, 951, 304	3, 269, 182	1, 849, 676	794, 627	10, 918, 253
Northern: BreakersWasheriesDredges	12, 165, 687	15, 173, 647	1, 639, 001	291, 136 168, 237	24, 067	29, 269, 471 168, 237 24, 067
Total Northern	12, 165, 687	15, 173, 647	1, 639, 001	459, 373	24, 067	29, 461, 775
Total, excluding Sullivan County: Breakers	14, 741, 459	30, 447, 027	9, 070, 933	2, 648, 273 2, 086, 791	1, 285, 033	56, 907, 692 2, 086, 791 1, 285, 033
TotalSullivan County: Breakers	14, 741, 459	30, 447, 027 48, 213	9, 070, 933	4, 735, 064	1, 285, 033	60, 279, 516 48, 213
Grand total	14, 741, 459	30, 495, 240	9, 070, 933	4, 735, 064	1, 285, 033	60, 327, 729

Table 16.—Culm-bank coal put through breakers, 1938-42, by fields, in net tons

Year	Northern	Eastern Middle	Western Middle	Southern	Total 1
1938	52, 000	11, 000	44, 000	455, 000	562, 000
1939	70, 000	17, 000	204, 000	295, 000	586, 000
1940	13, 000	139, 000	250, 000	362, 000	764, 000
1941	113, 000	57, 000	519, 000	387, 000	1, 076, 000
1942	291, 000	420, 000	1, 413, 000	524, 000	2, 648, 000

No culm-bank coal is put through breakers in Sullivan County.
 Includes some washery coal.

Table 17.—Pennsylvania anthracite shipped in 1942, by regions and sizes

			Breaker s	hipments 1					
Size					Т	otal	Washery	Dredge	Grand
	Lehigh region	Schuylkill region	Wyoming region	Sullivan County	Excluding Sullivan County	Including Sullivan County	shipments	shipments	total
Net tons									e 194
Lump 2 and Broken	48, 161 383, 080	40, 014 716, 184	49, 726 1, 563, 579	591	137, 901	138, 492 2, 662, 843			138, 492
Egg_ Stove. Chestnut. Pea	1, 914, 157 2, 077, 888 935, 372	3, 064, 140 3, 631, 354 1, 751, 738	7, 080, 423 7, 051, 684 2, 200, 667	2,472 7,177 7,422	2, 662, 843 12, 058, 720 12, 760, 926 4, 887, 777	12, 061, 192 12, 768, 103 4, 895, 199	50, 063 244, 145 104, 481	(3)	2, 662, 843 12, 111, 255 13, 012, 248 4, 999, 680
Total domestic sizes	5, 358, 658	9, 203, 430	17, 946, 079	17, 662	32, 508, 167	32, 525, 829	398, 689		32, 924, 518
Buckwheat No. 1. Buckwheat No. 2 (Rice)	1, 290, 503 759, 086 874, 317 372, 602 167, 099	2, 762, 553 1, 722, 576 2, 165, 725 918, 009 163, 479	3, 363, 951 1, 629, 833 1, 881, 539 375, 784 192, 980	5, 424	7, 417, 007 4, 111, 495 4, 921, 581 1, 666, 395 523, 558	7, 422, 431 4, 111, 495 4, 921, 581 1, 666, 395 526, 025	349, 909 27', 871 397, 134 456, 245 78, 078	3 16, 828 45, 689 198, 787 445, 016 71, 699	7, 789, 168 4, 435, 055 5, 517, 502 2, 567, 656 675, 802
Total steam sizes	3, 463, 607	7, 732, 342	7, 444, 087	7, 891	18, 640, 036	18, 647, 927	1, 559, 237	778, 019	20, 985, 183
Grand total	8, 822, 265	16, 935, 772	25, 390, 166	25, 553	51, 148, 203	51, 173, 756	1, 957, 926	778, 019	53, 909, 701
Value  Lump <sup>2</sup> and Broken Egg. Stove. Chestnut. Pea.	\$285,000 2,426,000 12,109,000 13,222,000 4,589,000	\$249,000 4,445,000 19,120,000 22,717,000 8,415,000	\$299, 000 9, 747, 000 44, 301, 000 44, 205, 000 10, 700, 000	\$2,000 10,000 29,000 23,000	\$833, 000 16, 618, 000 75, 530, 000 80, 144, 000 23, 704, 000	\$835, 000 16, 618, 000 75, 540, 000 80, 173, 000 23, 727, 000	\$268, 000 1, 298, 000 451, 000	(3)	\$835,000 16,618,000 75,808,000 81,471,000 24,178,000
Total domestic	32, 631, 000	54, 946, 000	109, 252, 000	64, 000	196, 829, 000	196, 893, 000	2, 017, 000		198, 910, 000
Buckwheat No. 1 Buckwheat No. 2 (Rice) Buckwheat No. 3 (Barley) Buckwheat No. 4 Other (including silt)	4, 512, 000 2, 045, 000 1, 720, 000 496, 000 136, 000	9, 396, 000 4, 363, 000 3, 899, 000 978, 000 132, 000	11, 726, 000 4, 414, 000 3, 685, 000 480, 000 167, 000	13,000	25, 634, 000 10, 822, 000 9, 304, 000 1, 954, 000 435, 000	25, 647, 000 10, 822, 000 9, 304, 000 1, 954, 000 436, 000	1, 090, 000 628, 000 676, 000 503, 000 77, 000	3 \$53,000 99,000 261,000 432,000 73,000	26, 790, 000 11, 549, 000 10, 241, 000 2, 889, 000 586, 000
Total steam	8, 909, 000	18, 768, 000	20, 472, 000	14, 000	48, 149, 000	48, 163, 000	2, 974, 000	918, 000	52, 055, 000
Grand total	41, 540, 000	73, 714, 000	129, 724, 000	78, 000	244, 978, 000	245, 056, 000	4, 991, 000	918, 000	250, 965, 000

Average value per ton	. 1	1						].	
Lump 2 and Broken	\$5.92	\$6.22	\$6.01	\$3.38	\$6.04	\$6.03			\$6.03
Egg_ Stove	6. 33 6. 33	6. 21 6. 24	6. 23 6. 26	4.05	6. 24 6. 26	6. 24 6. 26	\$5.35		6. 24 6. 26
Chestnut Pea	6.36 4.91	6. 26 4. 80	6. 27 4. 86	4. 04 3. 10	6. 28 4. 85	6. 28 4. 85	5. 32 4. 32	(3)	6. 26 4. 84
Total domestic	6. 09	5. 97	6. 09	3. 62	6. 05	6. 05	5. 06		6.04
Buckwheat No. 1 Buckwheat No. 2 (Rice) Buckwheat No. 3 (Barley) Buckwheat No. 4 Other (including silt)	3. 50 2. 69 1. 97 1. 33 . 81	3. 40 2. 53 1. 80 1. 07 . 81	3. 49 2. 71 1. 96 1. 28 . 87	2.40	3. 46 2. 63 1. 89 1. 17 . 83	3, 46 2, 63 1, 89 1, 17 , 83	8. 12 2. 26 1. 70 1. 10 . 99	3 \$3. 15 2. 17 1. 31 . 97 1. 02	3. 44 2. 60 1. 86 1. 13 . 87
Total steam	2. 57	2. 43	2. 75	1.77	2. 58	2, 58	1, 91	1.18	2. 48
Grand total	4.71	4, 35	5.11	3.05	4.79	4.79	2. 55	1.18	4.66

Figures of shipments from breakers include some culm bank coal handled in the breakers.
 Quantity of Lump included is insignificant.
 A small amount of Pea included in Buckwheat No. 1.

Table 18.—Sizes of Pennsylvania anthracite shipped from breakers, 1940-42, by regions, in percent of total

[Note that shipments of dredge and washery coal are not included]

	Percent of total shipments										
Size	Lel	nigh re	gion	Schuylkill region			Wyoming region				
	1940	1941	1942	1940	1941	1942	1940	1941	1942		
Lump <sup>1</sup> and Broken Egg. Stove. Chestnut. Pea.	3. 8 23. 3	0.5 3.5 23.1 24.1 11.6	0.6 4.3 21.7 23.6 10.6	0. 4 3. 9 19. 1 23. 3 11. 8	0.5 3.6 19.5 22.7 11.4	0,2 4,2 18,1 21,4 10,4	0. 2 5. 0 27. 0 27. 6 10. 6	0. 1 4. 7 27. 6 27. 7 10. 1	0. 2 6. 1 27. 9 27. 8 8. 7		
Total domestic	63.8	62.8	60.8	58. 5	57.7	54.3	70.4	70.2	70.7		
Buckwheat No. 1 Buckwheat No. 2 (Rice) Buckwheat No. 3 (Barley) Other, including Buckwheat No. 4 and Silt	8.3	15.4 8.4 8.9 4.5	14.6 8.6 9.9 6.1	16. 2 9. 3 11. 4 4. 6	16.3 9.7 11.4 4.9	16.3 10.2 12.8 6.4	13. 6 6. 9 7. 6 1. 5	13. 4 7. 2 7. 4 1. 8	13. 2 6. 4 7. 4 2. 3		
Total steam 2	36. 2	37. 2	39. 2	41.5	42. 3	45.7	29.6	29.8	29. 3		
						Tot	al—	. 1	-		
Size	Sulli	van <u>"</u> Co	ounty		ding Si County			ding Su County			
Lump <sup>1</sup> and Broken  Egg Stove Chestnut Pea  Total domestic  Buckwheat No. 1 Buckwheat No. 2 (Rice)	13. 8 18. 7 12. 6 45. 1	5. 3 14. 7 11. 9 31. 9	2.3 9.7 28.1 29.0 69.1 21.2	0.3 4.5 24.1 25.9 11.1 65.9	0.3 4.1 24.4 25.5 10.8 65.1	0.3 5.2 23.6 24.9 9.6 63.6	0.3 4.5 24.1 25.9 11.1 65.9	0.3 4.2 24.3 25.5 10.8 65.1	0. 3 5. 2 23. 6 24. 9 9. 6 63. 6		
Buckwheat No. 2 (Rice) Buckwheat No. 3 (Barley) Other, including Buckwheat No. 4 and Silt		7.4 57.0	9.7	7.8 8.8 2.8	8. 2 8. 9 3. 2	8.0 9.6 4.3	7.8 8.8 2.8	8. 2 8. 9 3. 2	8. 0 9. 6 4. 3		
Total steam	54.9	68.1	30. 9	34.1	34. 9	36. 4	34.1	34.9	36. 4		

<sup>&</sup>lt;sup>1</sup> Quantity of Lump included is insignificant. <sup>2</sup> Includes all steam sizes.

# AVERAGE SALES REALIZATION

The valuation figures in this study represent values at the breaker or washery as reported by the operating companies. The reporting companies are requested to "estimate value of the product not sold"

and to "exclude selling expenses" in making their reports.

From this it will be seen that when a producing concern sells its output to a separately organized sales company, the value reported will exclude the margin of the sales company and may therefore be somewhat less than the circular price at which the coal is placed on the general market. This fact should be borne in mind in considering the variations in value among different regions, shown in tables for the same sizes of coal.

The average sales realization per net ton on breaker shipments was \$4.79 in 1942 compared with \$4.59 in 1941 (see table 19). If local sales, colliery fuel, and washery and dredge coal are included, the average value per net ton of the total 1942 production was \$4.50 compared with \$4.26 in 1941 (see table 20).

4.79

Table 19.—Average sales realization per net ton on Pennsylvania anthracite ship-ments from breakers, 1940-42, by regions and sizes

[Value does not include margins of separately incorporated sales companies]

Size	Le	high re	gion	Schu	ıylkill ı	region	Wyo	ming r	egion
DIZE	1940	1941	1942	1940	1941	1942	1940	1941	1942
Lump 1 and Broken Egg Stove Chestnut Pea.	5. 27 5. 45 5. 51 4. 15	\$5. 61 5. 79 5. 92 5. 95 4. 53	\$5. 92 6. 33 6. 33 6. 36 4. 91	\$5.82 5.38 5.50 5.46 4.09	\$5.82 5.84 5.94 5.88 4.45	\$6. 22 6. 21 6. 24 6. 26 4. 80	\$5. 21 5. 30 5. 46 5. 50 4. 15	\$5. 61 5. 85 5. 93 5. 94 4. 52	\$6. 01 6. 23 6. 26 6. 27 4. 86
Total domestic	5. 23	5. 67	6.09	5. 19	5. 61	5. 97	5. 27	5. 72	6. 09
Buckwheat No. 1	2.32	3. 36 2. 54 1. 84	3.50 2.69 1.97	3. 16 2. 31 1. 59	3.34 2.43 1.67	3. 40 2. 53 1. 80	3. 19 2. 39 1. 75	3. 40 2. 59 1. 85	3. 49 2. 71 1. 96
Total steam 2	2. 37	2. 53	2. 57	2. 29	2, 42	2.43	2. 52	2.67	2.75
Total all sizes	4. 18	4. 50	4.71	3. 99	4. 26	4. 35	4. 45	4.82	5. 11
						Tot	al—		
Size	Sulli	van Co	ounty	Exclu	ding Si Count	ıllivan Y		ding St County	
Lump 1 and Broken  Egg. Stove. Chestnut. Pea.	\$4.31 4.29	\$4.09 3.69 2.73	\$3.38 4.05 4.04 3.10	\$5. 49 5. 32 5. 47 5. 49 4. 13	\$5. 72 5. 84 5. 93 5. 93 4. 50	\$6.04 6.24 6.26 6.28 4.85	\$5.49 5.32 5.47 5.49 4.13	\$5.72 5.84 5.93 5.93 4.50	\$6.03 6.24 6.26 6.28 4.85
Total domestic	4.02	3. 40	3. 62	5. 24	5. 68	6.05	5. 24	5. 68	6.05
Buckwheat No. 1.— Buckwheat No. 2 (Rice)————————————————————————————————————	2. 51 1. 10	1.45	2. 40	3. 18 2. 35 1. 68	3.37 2.52 1.78	3. 46 2. 63 1. 89	3. 18 2. 35 1. 68	3.37 2.52 1.78	3. 46 2. 63 1. 89
Total steam 2	1.08	. 95	1.77	2. 41	2. 55	2. 58	2. 41	2. 55	2. 58

Quantity of Lump included is insignificant.
 Includes all steam sizes.

Total all sizes\_\_\_\_\_

Table 20.—Average value per net ton of Pennsylvania anthracite shipments, local sales, colliery fuel, and total production, 1941-42, by regions <sup>1</sup>

[Note that values in this table include washery and dredge coal]

		19	941			19	<b>342</b>	
Region	Ship- ments	Local sales	Colliery fuel	Total produc- tion	Ship- ments	Local sales	Colliery fuel	Total produc tion
Lehigh Schuylkiii Wyoming	\$4.45 3.85 4.79	\$4.91 2.88 4.60	\$2.07 1.74 1.23	\$4.36 3.74 4.58	\$4.67 4.08 5.09	\$5. 24 2. 84 4. 72	\$2. 20 1. 84 1. 37	\$4. 60 3. 96 4. 85
Total, excluding Sullivan CountySullivan County	4. 41 1. 73	4. 02 2. 88	1. 45 . 84	4. 26 2. 24	4. 66 3. 05	4. 19 3. 15	1. 57 . 96	4. 50 3. 05
Grand total	4.41	4. 01	1.45	4. 26	4. 66	4. 19	1. 57	4. 50

<sup>&</sup>lt;sup>1</sup> Value given for shipments is value at which coal left possession of producing company and does not include margins of separately incorporated sales companies.

## LABOR STATISTICS

A labor shortage of several thousand men developed in the Pennsylvania anthracite industry in 1942, when the average number of men employed was 82,121—a decrease of 5,933 from the total of 88,054 men employed in 1941. Many men formerly employed in the anthracite mines entered the armed forces, and others obtained employment

in near-by war industries.

The employment statistics in this chapter do not include workers in "bootleg" or illicit coal mining, which is conducted in the Southern and Western Middle fields of the Pennsylvania anthracite regions. According to the Anthracite Committee, 10,762 men were working 3,006 "bootleg" holes in March 1941, and in May 1942 a comparable survey revealed 7,554 men employed in 2,029 holes. Although these workers are not included in the employment data, the coal produced by some of them was purchased by the legitimate industry for preparation and shipment to market, and coal so purchased is included in the production tables of this chapter. Complete employment data for the "bootleg" holes from which this coal was produced are not available. In calculating the output per man per day, therefore, the tons of "bootleg" coal purchased by the legitimate industry were deducted from the total tonnage reported by the operators, and the resulting legitimate production was then used to calculate the output per man per day. It is true that part of the time of the men employed at the preparation plants of the legitimate companies was used to prepare this purchased coal for market; however, on a per-ton basis this time is very small, and its omission will not detract materially from the validity of the result obtained.

See tables 21 to 23 for details on labor statistics.

Table 21.—Men employed and days worked at operations producing Pennsylvania anthracite in 1942, by regions 1 [Includes operations of strip contractors]

			Aver	age number	of men emplo	oyed					
Region	Underground				Surface				Average number of	Man-days of	Average tons per
-105-01	Miners and their laborers	Other	Total under- ground	In strip pits	In prep- aration plant	Other	Total surface	Grand total	days plant operated	labor	man per day
Lehigh: Breaker Washery Dredge	5, 510	4,012	9, 522	1, 206	1,015 35 2	2, 366 86 6	4, 587 121 8	14, 109 121 8	232 231 144	3, 272, 448 28, 009 1, 152	2. 95 2 9. 79 8. 15
Total Lehigh	5, 510	4, 012	9, 522	1, 206	1,052	2, 458	4,716	14, 238	232	3, 301, 609	3. 01
Schuylkill: Breaker Washery Dredge	7,827	4,831	12, 658	2, 616	1, 773 137 145	3, 139 533 274	7, 528 670 419	20, 186 670 419	231 198 230	4, 660, 336 132, 361 96, 526	* 3. 30 * 12. 42 12. 97
Total Schuylkill	7, 827	4, 831	12,658	2, 616	2, 055	3, 946	8, 617	21, 275	230	4, 889, 223	3.74
Wyoming: Breaker Washery Dredge	24, 468	12, 209	36, 677	704	2,322 29 11	6, 701 61 6	9,727 90 17	46, 404 90 17	245 119 280	11, 366, 460 10, 670 4, 760	2. 58 2 15. 77 5. 06
Total Wyoming	24, 468	12, 209	36, 677	704	2, 362	6, 768	9, 834	46, 511	245	11, 381, 890	2. 59
Total, excluding Sullivan County: Breaker	37, 805	21, 052	58, 857	4, 526	5, 110 201 158	12, 206 680 286	21, 842 881 444	80, 699 881 444	239 194 231	19, 299, 244 171, 040 102, 438	8 2. 81 8 12. 20 12. 54
TotalSullivan County: Breaker	37, 805 58	21, 052 11	58, 857 69	4, 526	5, 469 13	13, 172 15	23, 167 28	82, 024 97	239 209	19, 572, 722 20, 236	8 2. 95 2. 38
Grand total	37, 863	21, 063	58, 926	4, 526	5, 482	13, 187	23, 195	82, 121	239	19, 592, 958	8 2. 95

Table 22.—Men employed at operations producing Pennsylvania anthracite, 1941-42, by counties

[Includes operations of strip contractors]

	[LHOIG.	200 Operations	or surip contractors		
County	М	en	County	М	en
Conney	1941	1942	County	1941	1942
Carbon Columbia Dauphin and Lebanon Lackawanna Luzerne Northumberland Schuylkili Sullivan	5, 058 444 861 15, 153 42, 773 6, 494 16, 940 89	4, 887 1, 004 1 603 14, 162 38, 868 6, 413 15, 918 97	Snyder, Susquehanna, and Wayne Berks, Lancaster, North- ampton, Perry, and York <sup>2</sup>	\$ 118 88, 054	74 95 82, 121

<sup>&</sup>lt;sup>1</sup> None in Lebanon County in 1942. <sup>2</sup> None in Perry County in 1941.

Table 23.—Strikes, suspensions, and lock-outs in Pennsylvania anthracite region in 1942

	Lehigh	Schuyl- kill	Wyoming	Total, ex- cluding Sullivan County	Sullivan County	Grand total
Total men employed	14, 238 7, 886 130, 599	21, 275 3, 222 26, 385	46, 511 15, 523 122, 657	82, 024 26, 631 279, 641	97	82, 121 26, 631 279, 641
Per man employed	9. 2 16. 6	1. 2 8. 2	2. 6 7. 9	3. 4 10. 5		3. 4 10. 5

## EQUIPMENT AND METHODS OF MINING

Mechanical loading.—The quantity of coal loaded mechanically underground increased from 13,442,000 net tons in 1941 to 14,741,000 tons in 1942. Hand-loaded tonnage amounted to 30,435,000 tons in




FIGURE 2.—Relative growth of mechanical loading, hand loading, and stripping of Pennsylvania anthracite, 1927-42.

<sup>&</sup>lt;sup>2</sup> Counties producing dredge coal only.

1941 and increased to 30,495,000 in 1942. Details are shown in tables 24 to 26. Figure 2 illustrates graphically the relative growth of underground mechanical and hand loading and of stripping in the Pennsylvania anthracite region, 1927–42.

Cutting machines.—The quantity of anthracite cut by machines increased from 1,855,000 net tons in 1941 to 2,286,000 tons in 1942.

Details are shown in table 27.

Table 24.—Relative growth of mechanical loading, hand loading, and stripping in Pennsylvania anthracite mines, 1938-42

[Mechanical loading includes coal handled on pit-car loaders and hand-loaded face conveyors]

			Net tons		Index n	umbers: 192	7=100
	Year	Mechanical loading un- derground	Stripping	Hand loading	Mechanical loading un- derground	Stripping	Hand loading
1938 1939 1940 1941 1942		10, 152, 000 11, 774, 000 12, 326, 000 13, 442, 000 14, 741, 000	5,095,000 5,486,000 6,353,000 7,317,000 9,071,000	27, 990, 000 30, 798, 000 29, 191, 000 30, 435, 000 30, 495, 000	457 530 554 605 663	237 255 295 340 421	39 43 41 43 43

Table 25.—Pennsylvania anthracite handled by mobile loaders and scrapers and by all types of conveyors in 1942, by fields, in net tons

Field	Séraper loaders	Pit-car loaders	Hand-loaded face con- veyors, all types <sup>1</sup>	Total me- chanically loaded un- derground
Northern Eastern Middle Western Middle Southern	2, 311, 019 202, 955 356, 272 1, 680	267, 304 270 21, 206 30, 784	9, 587, 364 612, 729 1, 328, 876 21, 000	12, 165, 687 815, 954 1, 706, 354 53, 464
	2, 871, 926	319, 564	11, 549, 969	14, 741, 459

<sup>&</sup>lt;sup>1</sup> Shaker chutes, etc., including those equipped with duckbills.

Table 26.—Pennsylvania anthracite loaded mechanically underground, 1938-42

Year	Sc	rapers		rs and pit-car aders <sup>1</sup>	Total loaded mechan- ically		
A VOIC	Number	Net tons	Number	Net tons	Number	Net tons	
	of units	loaded	of units	handled	of units	handled	
1938	545	2, 589, 954	2 1, 831	<sup>2</sup> 7, 561, 715	2, 376	10, 151, 669	
	535	3, 088, 956	1, 997	8, 684, 877	2, 532	11, 773, 833	
	2 547	2, 983, 792	2, 189	9, 342, 208	2, 736	12, 326, 000	
	2 505	2, 673, 983	2, 432	10, 768, 004	2, 937	13, 441, 987	
	2 524	2, 871, 926	2, 491	11, 869, 533	3, 015	14, 741, 459	

<sup>&</sup>lt;sup>1</sup> Includes duckbills and other self-loading conveyors, which handle only a small part of the total.
<sup>2</sup> Includes mobile loaders.

Table 27.—Pennsylvania anthracite cut by machines, 1941-42, by regions

		1941			1942	
Region	Cutting machines Net tons			Cutting	Net tons	
	Permis- sible	All other types	cut by	Permis- sible	All other types	cut by machines
LehighSchuylkill					3	21, 907
Wyoming	161	61	1, 855, 422	153	85	2, 263, 733
Total, excluding Sullivan County Sullivan County	161	61	1, 855, 422	153	88	2, 285, 640
Grand total	161	61	1, 855, 422	153	88	2, 285, 640

Strip-pit operations.—The demand for anthracite caused a rapid expansion of strip-pit activities, and the tonnage recovered by this method of mining increased from 7,317,000 net tons in 1941 to 9,071,000 tons in 1942. In 1942, 16.7 percent of the fresh-mined coal was recovered from strip pits compared with 14.3 percent in 1941. For details of strip pit mining see table 28. Figure 3 illustrates graphically the production of anthracite from strip pits, by regions, 1927–42.




FIGURE 3.—Pennsylvania anthracite mined from strip pits, by regions, 1927-42.

Dredge operations.—Anthracite recovered from the rivers and creeks draining the anthracite fields totaled 1,285,000 net tons in 1942, a decrease from 1,518,000 tons in 1941. For detailed statistics by rivers see table 29.

Table 28.—Relative growth of Pennsylvania anthracite mined from strip pits, 1915, 1920, 1925, 1930, and 1939-42

	Number of power Net tons mined by stripping			Percent of fresh-mined	Number	Average number
	shovels in use <sup>1</sup>	Total	Average per shovel	total that was stripped	of men employed	of days worked
1915 1920 1925 1925 1930 1939 1940 1941	57 96 97 108 346 348	1, 121, 603 2, 054, 441 1, 578, 478 2, 526, 288 5, 486, 479 6, 352, 700 7, 316, 574	19, 677 21, 400 16, 273 23, 484 15, 857 18, 255 (2)	(2) 2. 5 2. 7 3. 7 11. 4 13. 3 14. 3	(2) (2) (2) (2) (2) 3,924 4,114 4,609	(2) (2) (2) (2) (2) 156 190
1942: Lehigh regionSchuylkill region Wyoming region	(2) (2) (2)	2, 261, 370 5, 170, 562 1, 639, 001	(2) (2) (2)	24. 7 32. 1 5. 6	1, 206 2, 616 704	214 206 226
Total, 1942	(2)	9, 070, 933	(2)	16.7	4, 526	21

<sup>&</sup>lt;sup>1</sup> Certain equipment reported by stripping contractors may have been counted twice when moved from one small job to another during the year. The amount of such double counting is unknown but presumably is not great.

<sup>2</sup> Data not available,

Table 29.—Pennsylvania anthracite produced by dredges in 1942, by rivers

River (including tributaries)				Net tons	Value		
		<b>1110 (1101)</b>		THE COLLS	Total	Average	
Lehigh Schuylkill Susquehanna				9, 385 268, 919 1, 006, 729	\$11, 246 320, 612 1, 146, 861	\$1. 20 1. 19 1. 14	
				1, 285, 033	1, 478, 719	1, 15	

### FOREIGN TRADE 2

Anthracite exported from the United States in 1942 totaled 4,438,589 net tons compared with 3,380,189 tons in 1941. Virtually all of the exported coal was shipped to Canada where shortages of heating gas and coke created a strong demand for anthracite. The tonnage exported in 1942 was the largest since 1923 when the total exports were 5,090,000 net tons. Details of imports and exports are shown in tables 30 to 32.

Canadian market.—Coal available for consumption in Canada in 1942 (changes in stocks not considered) increased about 10.5 percent over 1941 and set an all-time high record. Increases were shown in each category—production, imports, and exports. Production of bituminous coal, subbituminous coal, and lignite increased nearly 3.4 percent; imports of anthracite 22 percent and of bituminous coal 16.5 percent. Although country of origin is not disclosed, virtually all of the anthracite and bituminous coal originated in the United States. Exports of bituminous coal increased more than 53 percent.

Although not disclosed by the Canadian records, United States Custom House statistics show that imports of coal from Canada are mainly into the Maine and New Hampshire and the Montana and

<sup>&</sup>lt;sup>2</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Idaho custom districts and that in 1942 imports into Montana and Idaho were more than 220,000 tons—an increase of 77 percent over 1941. A large part of this tonnage probably was for consumption in the State of Washington. American consuls report a marked decline in coal production in British Columbia in the first part of 1943 as compared with 1942.

See table 33 for statistics on coal and coke in Canada.

Table 30.—Anthracite imported for consumption in the United States, 1941-42, by countries and customs districts, in net tons

	1941	1942		1941	1942
Country			Customs district		
CanadaUnited KingdomU. S. S. R	947 73, 722	140, 707 67	Los Angeles Maine and New Hampshire Massachusetts	902 66, 993 45	67 62, 923 61, 243
	74, 669	140, 774	Montana and Idaho New York Rhode Island	6, 729	1, 330 15, 211
				74, 669	140, 774

Table 31.—Anthracite exported from the United States, 1941-42, by countries, in net tons

Country	1941	1942	Country	1941	1942
North America:  Bermuda Canada Leeland Central America: British Honduras Guatemala Nicaragua Panama Mexico Newfoundland and Labrador West Indies: British Cuba Curacao (N. W. I.) Dominican Republic	1, 101 3, 360, 515 40 1 22 114 4, 720 272 262 81 56	4, 417, 689 1, 988 	North America—Con.  West Indies—Com Jamaica Other North America South America: Bolivia. Brazil Colombia Surinam Other South America Europe: Portugal United Kingdom <sup>1</sup> Asia. Africa	9, 624 85 987 11 1, 205 728 209 3, 380, 189	2, 571 19 2, 836 10, 210 6 88

<sup>&</sup>lt;sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

Table 32.—Anthracite exported from the United States, 1941-42, by customs districts and ports of export, in net tons

Customs district	1941	1942	Customs district	1941	1942
North Atlantic: Connecticut Maine and New Hampshire. Massachusetts New York Philadelphia South Atlantic: Maryland Virginia Gull coast: Florida Mobile New Orleans Mexican border: Arizona El Paso	2, 923 99 27, 512 22, 242 204 132 41 36 20	45 15, 743 169 24, 864 14, 879 2, 621 	Mexican border—Con. Laredo	575 40 72 1, 958, 665 106 4, 070 15, 832 16, 513 366, 799 956, 892 7, 416 3, 380, 189	264 56 64

Table 33.—Coal and coke industry and foreign trade of Canada, 1941-42, in thousands of net tons

				Co	oal					
	Anthracite		Bituminous and subbituminous		Lignite		Total		Coke from coal	
	1941	1942	1941	1942	1941	1942	1941 1	1942 2	1941 1	1942 2
ProductionImportsExports	3, 941	4,802	14, 188 17, 867 525	14, 316 20, 807 806	4, 034 1 7	4, 523	18, 222 21, 809 532	18, 839 25, 609 816	3, 150 614 40	3, 275 720 45
Available for consumption	3, 941	4, 802	31, 530	34, 317	4, 028	4, 513	39, 499	43, 632	3, 724	3, 950

1 1941 Quarterly Report (December) on coal and coke statistics for Canada; coal used in making coke, 4,360,583 tons, of which 2,865,274 tons imported:

2 Monthly coal and coke statistics for Canada, December 1942; coal used in making coke, 4,537,524 tons of which 2,983,460 tons imported.

# WORLD PRODUCTION

Data on world production of anthracite are incomplete because of war conditions throughout the world. Available data for 1937-42 are shown in table 34.

Table 34.—World production of anthracite, 1937-42, in metric tons

	[Com <sub>]</sub>	oiled by B. I	3. Waldbauer	<b>:</b> ]		
Country	1937	1938	1939	1940	1941	1942
BelgiumBulgaria	6, 694, 049 2, 542	6, 874, 520 4, 000	(1) 6, 038	(1)	(1)	(1)
China	(2), 012	(1)	(1)	8,000	13	(1)
Chosen	1, 101, 500	1,664,000	2, 064, 000	$\mathbb{R}$	1 33	<u>(3)</u>
France	(2)	(1)	2,001,000	K	X	
Germany		(1)	(1)	运	K	$\mathbb{R}$
Indochina		2, 289, 832	2, 534, 000	2,400,000	M	l X
Irish Free State		92, 157	90, 455	74, 170	104,871	\ \?\\
Italy		132, 197	100,000	(1)	(1)	16
Japan 3		(1)	(1)	(1)	(1)	(1)
Morocco, French		123, 200	115,600	4 143, 000	4 139,000	4 5 110,000
Peru		1,500	3, 514	4,500	4,600	(1)
PortugalRumania		281, 740	294, 081	286, 854	436, 324	6 349, 377
Spain	3,646	3, 266	(1)	(1)	(1)	(1)
Switzerland	407, 838 4, 000	440, 253	506, 109	1,095,875	1, 170, 132	7 713, 503
U. S. S. R.:	4,000	3,000	2,500	7,000	(1)	\$ 40,000
Asiatic	(2)	/IV	71)			
European	2	$\aleph$	X			(2)
United Kingdom	6, 437, 465	6, 378, 904	Ж	$\mathbb{R}$	1 23	1 8
United States	47,043,119	41, 820, 115	46, 708, 319	46, 705, 836	51, 136, 164	54, 728, 109
				10,100,000	01, 100, 101	04, 720, 109
World total	113, 171, 119	(1)	(1)	(1)	(1)	(1)
Total, exclusive of	' '			`,		
United States	66, 128, 000	(1)	(1)	(1)	(1)	(1)
		· · · · · ·	.,	.,	' '	

Data not available.


Base not available.
 Estimate included in total.
 Anthracite output of Japan said to average about 225,000 tons a year. Production figures not available.
 Production of Djerada Basin only.

Formated.

5 Estimated.

6 January to October, inclusive.

7 January to July, inclusive.



# **COKE AND BYPRODUCTS**

By J. W. Buch, J. A. DE CARLO, AND M. M. OTERO

### SUMMARY OUTLINE

	Page		
Summery	Tago		Page
Government control measures		Coke and coke breeze—Continued.	
Technologic developments	953	Stocks of coke and coking coal	980
Salient statistics		I Value and Drice	982
Statistical trends	955	Suldments by rail, water, and truck	004
Scope of report		Distribution of byproduct and beebive	
Coke and coke breeze	957	i coke	004
Monthly and weekly production	958	Exports and imports	080
Production by furnous and	958		
Production by furnace and nonfurnace plants		Gas-house coke	001
Production by States and districts	961	Uoke-oven hyproducts	000
Number and type of orem	962	Summary of byproducts	002
Number and type of ovens	965		
Capacity of byproduct plants	967	1 81	
Quantity and cost of coal charged			
Preparation and source of coal		Light oil and its derivatives	1001
Yield of coke per ton of coal		Naphthalene	1001
Coke breeze		Byproduct coke ovens owned by city gas	1001
Consumption of coke	977	companies	
Furnace, foundry, domestic, and other coke			1001
COAG	978		

# SUMMARY.

The year 1942 witnessed a new high coke-production record for the United States in response to the heavy demand of the expanded iron and steel industry for metallurgical fuel. The total output of byproduct and beehive coke was 70,568,944 net tons—an increase of 5,382,366 tons (8 percent) over the last previous high record in 1941. Of the amount of coke produced in 1942, byproduct ovens supplied 62,294,909 tons (88 percent) and beehive ovens 8,274,035 tons (12 percent). Byproduct-coke production increased 3,812,487 tons (7 percent) in 1942 compared with 1941, and the production of beehive coke increased 1,569,879 tons (23 percent). The average daily rate of byproduct output increased steadily throughout the year; the average daily rate of beehive remained fairly constant.

Although the 1942 output from beehive ovens represented only 12 percent of the Nation's total coke production, its contribution to the 1942 war program was noteworthy. Of the 7,309,337 tons of beehive coke produced in Pennsylvania, 6,561,085 tons (90 percent) were used in blast furnaces (table 28), mostly in the Pittsburgh district, where pig iron production would have been seriously hampered without the

supply from nearby beehive-coke plants.

The total value of coke, breeze, and tar produced and of other by-products sold in 1942 was \$629,408,422 (an increase of 17 percent over 1941) and exceeded that of any previous year. The greatest increase was in the value of byproduct coke produced, which rose from \$316,477,231 in 1941 to \$378,011,967 in 1942—an increase of




FIGURE 1.—Average daily production of beehive and byproduct coke and pig iron and producers' stocks of byproduct coke, 1935-43, by months.

を持て事件が一次の子は、文心を強性を切り、一次の意思である。

19 percent; the value of byproducts sold rose from \$158,809,184 to \$176,932,465—an increase of 11 percent for the same period.

The production of screenings or breeze in 1942 was 4,751,683 tons and exceeded the 1941 output by 197,170 tons; the average receipts from sales of breeze increased from \$2.35 a ton in 1941 to \$2.63 in 1942.

The total calculated consumption of coke for all uses in the United States in 1942 was 70,107,181 tons. The principal use was in blast furnaces, and the quantity used by the producers, sold to financially affiliated corporations, or sold to other companies for blast-furnace use was 55,491,570 tons—an increase of 5,037,245 tons (10 percent) over the 1941 figure. Coke used for other purposes (in foundries, for the manufacture of producer gas and water gas, and for other industrial purposes) totaled 9,190,418 tons. Coke sold for domestic use was reported as 6,061,694 tons compared with 6,682,959 tons in 1941. The continued decrease in the quantity of coke used for domestic heating in 1942 emphasized the demand of the iron and steel industry.

Ceiling prices for coke were established by the Office of Price Administration on issuance of Maximum Price Schedules 29, 77, and 121, with subsequent amendments. The average receipts per ton of coke sold by producers in 1942 were as follows: Furnace, \$6.16 per ton—an increase of \$0.53 over 1941; foundry coke, \$9.75—\$0.40 higher than the 1941 price; coke used in the manufacture of water gas, \$7.53—\$0.79 higher than the price in 1941; other industrial, \$6.88—an advance of \$0.50 above the 1941 price; and domestic coke, \$7.84—an

increase of \$0.91.

Total requirements in 1942 exceeded the output, and producers' stocks of coke totaled 1,489,049 tons at the end of the year—a reduction of 269,037 tons in stocks. Stocks of domestic coke decreased

344,285 tons; stocks of furnace coke increased 76,543 tons.

The accelerated rate of byproduct-coke-oven operations resulted in substantial increases in the output of gas, tar, crude light oil, and ammonia. The quantity of gas produced totaled 944,879,637 M cubic feet in 1942—a gain of 52,059,826 M cubic feet (6 percent) over the 1941 figure. Crude coal-tar output showed an increase of 36,026,-151 gallons (5 percent) and reached an all-time record of 740,175,619 gallons.

Production of ammonium sulfate or equivalent increased from 1,741,503,884 pounds to 1,805,025,721 pounds (4 percent); the production of crude light oil increased from 231,358,897 gallons to 246,024,882

gallons (6 percent).

### GOVERNMENT CONTROL MEASURES

The importance of coke and coke byproducts in time of war was recognized by the various war agencies, and a number of regulatory measures were established for the conservation, efficient utilization, and price control of the products derived from the carbonization of coal. A brief summary of the more important regulations follows:

Byproduct coke.—Office of Price Administration Maximum Price Schedule 29, issued August 30, 1941, effective October 1, 1941, froze prices of byproduct-foundry and byproduct-furnace coke at the levels prevailing October 1, 1941. Amendment 1, issued February 4, 1942, and effective February 7, equalized regional prices not covered in the original order; Amendment 2, issued January 28, 1943, retroactive to December 1, 1942, allowed the transportation-tax charge

of not more than 4 cents per ton of coke to be passed on to consumers, provided that the producers had paid a similar tax on the coal used to

produce the coke.

Beehive coke.—Maximum Price Schedule 77, effective January 26, 1942, established a \$6.00 per ton price on all beehive-furnace coke produced in Pennsylvania. Amendment 1 to revised Price Schedule 77, effective April 11, 1942, established a provision in which adjustments and exceptions could be presented; Amendment 2, effective August 12, raised the price to \$6.50 for hand-drawn coke, where coal was trucked; Amendment 3 allowed the transportation-tax charge of not more than 4 cents per ton of coke to be passed on to consumers, provided that the coke-plant operator had paid a similar tax on coal charged into ovens.

In order that ceiling prices on all other coke produced not covered by Schedules 29 and 77 could be established, Maximum Price Schedule 121 was issued, effective May 18, 1942, which established maximum prices upon the basis of average prices over the period from December

15 to 31, 1941.

Benzol.—War Production Board General Preference Order M-137, issued April 20, 1942, effective June 1, placed benzol under complete allocation. This order was amended July 1, and deliveries and acceptances were placed under the supervision of the Director General for Operations. In December 1941 quotations on benzol, toluol, and xylol were stablized at not more than 1 cent a gallon above the average for the last quarter of 1941 at the request of the Office of Price Administration, and on March 11 this request was extended to keep current quotations in effect at least until July 1, 1942. In June 1942 the Office of Price Administration announced that quotations on light-oil derivatives would remain unchanged to December 31, 1942.

Toluol.—General Preference Order M-34, issued August 8, 1941, effective August 28, 1941, placed toluol under allocation. Amendments effective December 30, 1941, and May 22, 1942, further restricted uses and increased regulations, and beginning early in January 1942 no toluol could be exported without authorization from the

Director of Priorities.

Xylol.—Xylol and xylol-range aromatic materials derived from coal tar were brought under General Preference Order M-150 by the issuance, in July 1942, of Amendment 1. This amendment restricted sales and deliveries of xylol and xylol-range aromatic materials to orders with a preference rating of A-2 or higher.

Ammonium sulfate.—This byproduct was placed under allocation by the War Production Board on June 1, 1942, through the issuance of General Preference Order M-163. Maximum prices for ammonium sulfate were governed by Maximum Price Schedule 205, issued by the

Office of Price Administration, effective August 22.

Pyridine.—Production and distribution of pyridine were placed under complete allocation by the War Production Board through Conservation Order M-185, effective September 1. In addition to its use in the manufacture of sulfa drugs, pyridine is employed in manufacturing a water repellant.

#### TECHNOLOGIC DEVELOPMENTS

War activities in 1942 augmented the demand for metallurgical coke. Iron-production requirements emphasized the need for the

pest possible grade of coke for blast-furnace use. The Bureau of Mines undertook investigations to assist the coke producers to meet the needs of blast furnaces as to available supply and quality. industry committee, working in cooperation with the Office of Solid Fuels Coordinator for War, the War Production Board, and the Bureau of Mines, advises the investigators of the most pressing needs and through cooperation and advice facilitates the research work to be done.

The addition of 4 percent of anthracite fines (No. 5 Buckwheat) to the coking-coal mix was practiced at the Laclede Gas Light Co., St. Louis, Mo., in 1942. It was reported that the quantity of largesize foundry coke produced doubled and that it was possible to carbonize 13 percent more coal per day because the coking time normally

required for foundry coke was reduced from 26 hours to 18%.2

Extensive research work was done in 1942 by the Koppers Co. concerning new methods of heating Koppers-Becker coke ovens The new heating methods were radical in departure from methods used in former years by this company, and it is reported that the research resulted in a coke-oven design that not only improved coke quality but also permitted more efficient economics of oven operation by simplifying operating technique.3

Table 1.—Salient statistics of the coke industry in 1942

	Byproduct	Beehive	Total
Coke produced—			
At merchant plants: Quantitynet tons	15, 134, 866		15, 134, 866
Value	\$114, 723, 148		\$114, 723, 148
Value			
Ouentity net tons.			47, 160, 04
Value	\$263, 288, 819		\$263, 288, 819
Total:		0.054.005	70 F00 04
Total: Quantitynet tons	62, 294, 909	8, 274, 035	70, 568, 944
	\$378, 011, 967	\$47, 601, 777	\$425, 613, 744
Value	4 000 000	151 659	4, 751, 68
Quantitynet tons	4,600,030	151, 653 \$151, 210	\$11, 048, 33
Value	\$10, 897, 121	\$131, 210	ф11, 040, 00
Coal charged into ovens:	87, 973, 821	12, 875, 812	100, 849, 63
Quantity	\$385, 007, 197	\$32, 458, 011	\$417, 465, 20
Value	\$4.38	\$2.52	\$4.1
Value	Ф±. 00	<b>42.02</b>	
Average yield in percent of coal charged:	70.81	64. 26	69. 9
CokeBreeze (at plants actually recovering)	5.30	2.46	5. 1
Breeze (at plants actually recovering)	0.00		
Ovens: In existence January 1	13, 016	18, 669	31, 68
In existence December 31	13, 303	1 16, 295	29, 59
In existence Determiner of		1,486	1, 62
Dismantled during year In course of construction December 31	1, 327		1, 32
Annual capacity of ovens December 31net tons	64, 554, 972	10, 408, 595	74, 963, 56
Coke used by producer—			
In blast furnaces:			40 004 8
In blast furnaces: Quantitynet tons	41, 602, 950	701, 830	42, 304, 78
Value	\$230, 691, 580	\$4, 028, 121	\$234, 719, 70
			810, 49
Quantityet cons	810, 492		\$5, 138, 2
Value	40, 200, 200		φυ, 100, Δι
To make water gas: Quantitynet tons	1 507 101		1, 527, 19
Quantitynet tons	1, 527, 191		\$8, 440, 5
Value	\$8,440,030		φυ, πευ, υ
For other purposes:	414,009	2, 305	416, 3
Valuenet tons_	\$2,504,247	\$12,420	\$2, 516, 60

<sup>1</sup> Number of ovens in existence at plants that operated in 1942 as reported by operators.

<sup>&</sup>lt;sup>1</sup> Schmidt, L. D., Schroeder, W. C., and Fieldner, A. C., Increased Pig Iron Output Through Improved Coke: Bureau of Mines Rept. of Investigations 3711, 1943, 58 pp.

<sup>2</sup> Roberts, I. M., Anthracite as a Coke Ingredient: Coal Age, vol. 47, No. 11, November 1942, p. 96.

<sup>3</sup> Rueckel, W. C., New Principles in Heating Koppers-Becker Coke Ovens: Blast Furnace and Steel Plant, vol. 30, No. 3, March 1942, pp. 331-337, and vol. 30, No. 4, April 1942, pp. 431-436.

Table 1.—Salient statistics of the coke industry in 1942—Continued

	Byproduct	Beehive	Total
Disposal of coke:			
Sold to financially affiliated corporations— For blast-furnace use:			
Quantitynet tons_	3, 515, 351	1, 542, 503	5, 057, 854
Quantity net tons.  Value  For other purposes:  Quantity net tons.  Value  Sold to other consumers—  For blast-furnace use:  Quantity pot tons	\$19, 373, 565	\$7, 570, 393	\$26, 943, 958
Quantitynet tons	729, 619	452	730, 07
Value	\$4, 638, 839	\$2,179	\$4,641,018
For blast-furnace use:			.,,,,,,
Quantitynet tons	3, 242, 612	4 886 324	8, 128, 936
Value For foundry use:	3, 242, 612 \$21, 337, 174	4, 886, 324 \$28, 714, 727	\$50, 051, 901
Quantitynet tons	2, 250, 564	341, 012	9 501 576
Quantitynet tons_ Value For manufacture of water gas:	\$22, 853, 858	\$2, 403, 220	2, 591, 576 \$25, 257, 078
Ouantity not tone	077 701	A STATE OF THE STA	等 化二二二十二十二十二十二十二十二十二十二十二十二十二十二十二十二十二十二十二十
Quantitynet tons_ Value For other industrial use:	657, 761 \$5, 131, 790	115, 265 \$691, 508	773, 026 \$5, 823, 298
For other industrial use:			
Quantitynet tons	1, 746, 562 \$12, 427, 915	595, 186 \$3, 688, 452	2, 341, 748
FOR COMESTIC USE:	100		\$16, 116, 367
Quantitynet tons	5, 963, 474 \$46, 967, 968	98, 220 \$544, 530	6, 061, 694
Disposal of screenings or breeze:	\$46, 967, 968	\$544, 530	\$47, 512, 498
Used by producer—			
Disposal of screenings or breeze:  Used by producer—  For raising steam:  Quantity———————————————————————————————————	9 100 000	20 000	0.440.004
Value	3, 123, 066 \$7, 008, 139	30, 029 \$40, 144	3, 153, 095 \$7, 048, 283
To make producer or water gas:		420,211	
Valuenet tons	46, 769 \$247, 952		46, 769 \$247, 952
For other purposes:			\$241, 952
Quantitynet tons_	509, 921 \$1, 054, 913	5, 741 \$6, 979	515, 662
8010:	\$1,054,913	\$6,979	\$1,061,892
Quantitynet tons	932, 122	62, 237 \$58, 200	994, 359
Value Verage receipts per ton sold:	\$2, 555, 985	\$58, 200	\$2, 614, 185
Furnace coke (merchant sales)	\$6. 58	\$5.88	\$6.16
For manufacture of water rec	\$6.58 \$10.15	\$7.05	\$9.75
Other industrial coke	\$7. 80 \$7. 12	\$6.00 \$6.20	\$7. 53 \$6. 88
Furnace core (merchant sales) Foundry coke For manufacture of water gas Other industrial coke Domestic coke Screenings or breeze tocks on hand January 1, 1943: Furnace net tons	\$7.88	\$5. 54	\$7.84
tocks on hand January 1, 1943:	\$2. 74	\$0.94	\$2.63
Furnacenet tons	770, 135	24, 617	794, 752
Domestic and other	21, 937	2, 203 8, 756 4, 956	794, 752 24, 140
Screenings or breeze do	655, 401 655, 175	8,756	670, 157 660, 131
exportsdodo			839, 582
tocks on hand January 1, 1943:   Furnace			108, 782 70, 107, 181
yproducts produced:			_
Wasted Wasted	944, 879, 637 1, 59 36, 45		944, 879, 637
Burned in coking processdo	1. 59 36. 45		1. 59 36. 45
Surplus sold or useddo	61. 96		61.96
Gas	740, 175, 619		740, 175, 619
Crude light oil gallons	1, 805, 025, 721 246, 024, 882		1, 805, 025, 721 246, 024, 882
ield of byproducts per ton of coal:			
TarM cubic feet_	10. 74 8. 41		10.74
Gas	20. 85		8. 41 20. 85
alue of byproducts sold:	2. 88		2. 88
Gas (surplus)	\$88, 823, 807		\$88, 823, 807
Tar:			
Sold	\$24, 155, 601		\$24, 155, 601
Ammonium sulfate or equivalent	\$15, 815, 882		\$15, 813, 882 \$21, 698, 572
Orthor hyproducts ?	\$15, 813, 882 \$21, 698, 572 \$29, 293, 280 \$12, 961, 205		\$21, 698, 572 \$29, 293, 280 \$12, 961, 205
otal value of coke and breeze produced and hyprod-	\$12, 961, 205		\$12, 961, 205
ucts sold 8	\$581, 655, 435	\$47, 752, 987	

Includes naphthalene and tar derivatives.
 Includes value of tar used by producer.

Table 2.—Statistical trends of the coke industry in the United States, 1923 and 1939-42

				7	
	1923	1939	1940	1941	1942
Coke produced:					
Beehivenet tons_	19, 379, 870	1, 444, 328	3, 057, 825	6, 704, 156	8, 274, 035
Byproductdo	37, 597, 664	42, 882, 313	54, 014, 309	58, 482, 422	62, 294, 909
TotaldoPercent of total from byproduct	56, 977, 534	44, 326, 641	57, 072, 134	65, 186, 578	70, 568, 944
ovens	66.0	96.7	94. 6	89. 7	88. 3
Producers' stocks of coke, end of year net tons	1 1, 221, 737	2, 602, 099	1, 956, 442	1, 758, 086	1, 489, 049
Exports, all coke do do Consumption, calculated, all coke do	1, 237, 342	589, 925	804, 095	708, 971	839, 582
Imports, all coke 2 do	85, 002	141, 911	112, 550	267, 886	108, 782
Consumption calculated all coke do	55, 173, 457	44, 953, 082	57, 026, 246	64, 943, 849	70, 107, 181
Disposal of coke, all coke sold or used:	ł	'' '	' '		
rurnace cokenet tons	47, 774, 408	31, 498, 557	42, 483, 624	50, 454, 325	55, 491, 570
Furnace coke net tons_ Foundry coke do Other industrial (including producer and	3, 600, 719	1, 682, 200	2, 089, 962	2, 846, 459	2, 591, 576
water gas)net tons	l * 2, 283, 888	3, 193, 068	3, 581, 676	4, 224, 597	5, 452, 457
Domestic cokedo	2, 733, 414	7, 638, 141	8, 231, 013	6, 682, 959	6, 061, 694
For all other purposesdo	(3)	1, 311, 559	1, 458, 435	1, 165, 526	1, 146, 385
Ovens:	100				
Beehive, in existence, end of year	62, 349	10, 934	15, 150	18, 669	4 16, 295
Byproduct, in existence, end of year	11, 156	12, 732	12, 734	13, 016	13, 303
Byproduct under construction, end of year	629		492	181	1, 327
Cost of coal charged, byproduct ovens,	100		100		
average per ton	\$4.76	\$3.75	\$3.68	\$3.92	\$4, 38
Prices of coke:					
Average spot price of Connellsville fur-	STATE OF STATE				
nace coke, f. o. b. ovens	\$5.33	\$4.09	\$4.42	\$5.92	\$6.01
Average realization on byproduct coke sold:					
Furnace coke (merchant sales)	\$6,74	\$4.38	\$4, 55	\$5, 70	\$6, 58
Foundry coke	\$10.54	\$8.15	\$8.67	\$9.76	\$10. 15
Other industrial (including water gas)	\$9.06	\$5.64	\$5, 86	\$6.68	\$7. 30
Domestic	\$0 05	\$5.90	\$6,03	\$6,96	\$7.88
Yield of byproducts per ton of coal charged: Targallons Ammonium sulfate or equivalent	40.00	40.00	45.55	40.00	
Tar gallons	8.1	9.06	8.79	8, 52	8, 41
Ammonium sulfate or equivalent		0.00	00	0.02	0
pounds	21. 2	22, 33	22, 00	21. 34	20, 85
Light oil gallons	2.7	2.99	2.93	2.90	2.88
Light oilgallons Surplus gas sold or used_M cubic feet	5.9	7.08	6.84	6.71	6. 65
Average gross receipts for byproducts, per	0.0		0.02		
ton of coke produced:			100		
Tar sold and used	\$0.51	\$0,622	\$0.571	\$0,566	\$0, 642
Ammonia and its compounds	\$0.84	\$0.341	\$0.364	\$0.371	\$0.348
Light oil and its derivatives (including	\$3.01	40.011	45.501	40.0.1	7
naphthalene)	\$0.51	\$0,414	\$0,421	\$0.431	\$0, 501
Surplus gas sold or used	\$1.37	\$1.676	\$1.507	\$1:454	\$1, 426
Total byproducts, including breeze		\$3.315	\$3.117	\$3, 130	\$3. 269
TOWN PAPER DEFORMATION TO THE PROPERTY OF THE PARENTY OF THE PAPER	ψυ, πο	40.010	40. TT!	40. 100	. 40. 200

tion only.

3 "For all other purposes" included under "Other industrial (including producer and water gas)."

4 Number of ovens in existence at plants that operated in 1942 as reported by operators.

### SCOPE OF REPORT

This report presents final statistics of the byproduct- and beehivecoke industry in 1942. In addition to the customary annual data, the results of a survey covering operations of coal-gas plants in 1942, made by the Bureau of Mines for the first time, are presented in this

chapter. In the United States coke is produced by a group of four different industries. In addition to that manufactured in the familiar byproduct and beehive ovens, coke is obtained in the refining of petroleum and of tar and in the manufacture of coal gas. The coke produced by each of these processes, however, differs greatly in character, and the problems affecting each are separate and distinct.

Furnace and foundry coke only.
 Before 1934, figures represent general imports; beginning with 1934, they represent imports for consump-

In 1942, 1,338,000 tons of petroleum coke and 117,714 tons of coal-tar-pitch coke were produced, compared with 1,648,000 and 91,800 tons, respectively, in 1941. The decrease in output of petroleum coke in 1942, in spite of increased requirements, was due to fuel-oil shortages, which forced several large refineries to eliminate coke production.

Since, in general, only coke from byproduct and beehive ovens is adapted to blast-furnace and foundry use and since most of all coke produced is directed to these uses, the coke trade is concerned more especially with byproduct and beehive coke; hence the statistics of this report relate especially to these two coke-manufacturing processes.

The standard unit of measurement in the coke industry is the short or net ton of 2,000 pounds, and unless otherwise specified that unit is

employed throughout this report.

## COKE AND COKE BREEZE

# MONTHLY AND WEEKLY PRODUCTION

Figures for monthly and weekly production of coke are given in tables 3 to 7. The monthly and weekly production of byproduct coke is based upon reports from operators. In February 1942 the Bureau of Mines renewed the collection of weekly production data from the byproduct-coke industry—the first time since 1918. This canvass was undertaken at the request of the Office of Solid Fuels Coordinator 4 for War in order that weekly production trends in the byproduct-coke industry could be ascertained. The demand for coke was so great in 1942 that maximum output was necessary to meet the increased requirements of the war industries, and the daily rate of production rose steadily throughout the year.

The current weekly statistics of beehive coke, shown in table 6, are estimates based upon weekly carloadings on the principal coke-carrying railroads, on shipments over private railroads, and on amounts known to have been consumed by associated steel works close to the producing ovens. As beehive coke seldom is stored at the ovens in any great quantity, shipments are a good barometer of weekly production. The collection of monthly data from beehive-coke-plant operators was begun by the Bureau of Mines in March 1942. Figures for January and February production are based upon operators'

reports of sales of beehive coke.

<sup>&</sup>lt;sup>4</sup> The Office of Solid Fuels Coordinator for War was changed by Executive order issued April 19, 1943, effective May 4, to Solid Fuels Administration for War.

Table 3.—Byproduct, beehive, and total coke produced in the United States, 1939-42, by months and average per day, in net tons

	193	9	194	0	194	1	194	2
Month	Total	Daily average	Total	Daily average	Total	Daily average	Total	Daily average
Byproduct:	1. 1. 4. 1. 1. 1. 1. 1. 1.		1		70 00	4.34		
January	3, 355, 200	108, 200	4, 720, 600	152, 300	4, 938, 800	159, 300	5, 228, 900	168, 700
February	3,066,800	109, 500	4,028,300	138, 900	4, 507, 400	161,000	4, 720, 300	168, 600
March April	3, 425, 700	110, 500	4, 136, 600	133, 400	5,005,200	161, 500	5, 230, 700	168, 700
April	2, 903, 800	96, 800	3, 995, 800	133, 200	4, 479, 600	149, 30u	5,060,400	168, 700
May June	2, 387, 100	77,000	4, 256, 000	137, 300	4,851,600	156, 500	5, 265, 600	169, 900
June	3, 078, 500	102,600	4, 387, 200	146, 200	4,841,700	161, 400	5, 104, 600	170, 200
July	3. 354. 100	108, 200	4, 632, 400	149, 400	5, 019, 600	161, 900	5, 282, 800	170, 40 171, 60
August September	3, 652, 900	117,800	4, 695, 500	151, 500	5,018,900	161, 900	5, 320, 000	172, 300
September	3, 890, 600	129,700	4, 640, 700	154,700	4,811.400	160, 400	5, 168, 400	172, 400
October	4, 512, 300	145, 600	4, 853, 600	156,600	4, 976, 500	160, 500	5, 343, 800	173, 200
November	4, 551, 900	151,700	4, 763, 500	158, 800	4, 839, 200	161, 300	5, 196, 000	173, 300
December	4, 703, 400	151, 700	4, 904, 100	158, 200	5, 192, 500	167, 500	5, 373, 400	175,500
	42, 882, 300	117, 500	54, 014, 300	147,600	58, 482, 400	160, 200	62, 294, 900	170, 700
Beehive:								
January	78, 400	3,000	252, 300	9,300	542, 500	17, 500	675, 400	21,800
Fohmowr	72,000	3,000	164, 400	6,600	523, 900	18, 700	635, 500	22,700
February March	69, 600	2,600	143, 100	5,500	618, 100	19, 900	694, 400	22, 40
Anril	20,000	800	108, 400	4, 200	98, 200	3, 300	686,600	22,900
May	24,700	900	112, 300	4, 200	571, 200	18, 400	700, 200	22,60
April May June	52, 300	2,000	159, 800	6,400	595, 400	19, 800	719,000	24,00
Inlv.	47, 100	1,900	244, 400	9,400	610, 400	19, 700	692, 800	22, 30
August September	44, 900	1,700	294, 200	10,900	644, 500	20,800	696, 700	22,50
September	77,000	3,000	287, 800	11,500	605, 800	20, 200	697, 600	23, 30
October	1 266, 800	10,300	384, 200	14, 200	646, 800	20, 900	722, 100	23, 30
November	362,700	14,000	416, 800	16,000	561, 300	18, 700	667, 400	22, 20
November December	328, 800	13, 200	490, 100	19,600	686, 100	22, 100	686, 300	22, 10
	1, 444, 300	4,700	3, 057, 800	9,800	6, 704, 200	18, 400	8, 274, 000	22,70
Total coke:								
January	3, 433, 600	111, 200	4, 972, 900	161,600	5, 481, 300	176, 800	5, 904, 300	190, 50
February	3, 138, 800	112, 500	4, 192, 700	145, 500	5, 031, 300	179, 700	5, 355, 800	191, 30
February March	3, 495, 300	113, 100	4, 279, 700	138, 900	5, 623, 300	181, 400	5, 925, 100	191, 10
April	2, 923, 800	97, 600	4, 104, 200	137, 400	4, 577, 800	152, 600	5, 747, 000	191,60
May	2, 411, 800	77, 900	4, 368, 300	141,500	5, 422, 800	174, 900	5, 965, 800	192, 50
April May June	3, 130, 800	104,600	4, 547, 000	152,600	5, 437, 100	181, 200	5, 823, 600	194, 20 192, 70
JIIIV	3.401.200	110, 100	4, 876, 800	158, 800	5, 630, 000	181,600	5, 975, 600	194, 10
August September	3, 697, 800	119,500	4, 989, 700	162, 400	5, 663, 400	182,700 180,600	6, 016, 700 5, 866, 000	195, 60
September	3,967,600	132,700	4, 928, 500	166, 200 170, 800	5, 417, 200 5, 623, 300	181, 400	6, 065, 900	195, 70
October	4,779,100	155, 900	5, 237, 800		5, 400, 500	180,000	5, 863, 400	195, 40
November	4, 914, 600	165, 700	5, 180, 300 5, 394, 200	174, 800 177, 800	5, 878, 600	189,600	6,059,700	195, 40
December		164, 900			·			
	44, 326, 600	122, 200	57, 072, 100	157, 400	65, 186, 600	178, 600	70, 568, 900	193, 40

<sup>&</sup>lt;sup>1</sup> Daily average production of beehive coke prior to 1941 was calculated by subtracting Sundays and holidays in each month: 1941 and 1942 daily average has been calculated by dividing the total monthly production by the total number of days in the month.

Table 4.—Byproduct coke produced in the United States in 1942, by weeks

[Based upon reports from all producers] Week ended-Net tons Net tons Week ended-Week ended-Net tons 1, 210, 000 1, 210, 200 1, 213, 700 1, 211, 000 1, 207, 600 1, 211, 200 1, 223, 400 1, 193, 900 1, 198, 300 1, 187, 800 1, 186, 700 1, 189, 100 1, 193, 900 5, 228, 900 1, 176, 700 1, 171, 000 1, 172, 900 1, 164, 200 1, 167, 500 1, 170, 000 1, 173, 300 September 26 May 30 June 6. February March 7 November 192,000 199, 600 204, 500 206, 600 December 700 1, 162, 500 169,000 213, 800 1, 223, 000 2 855, 900 1, 175, 400 1, 186, 900 1, 185, 300 220, 100 215, 500 September 5 62, 294, 900 19.

Weekly statistics of byproduct-coke production were not collected until the week ended February 7, 1942.
 5 days only.

Table 5.—Byproduct coke produced in the United States in 1942, by months and States, in net tons

[Based upon reports from all producers]

State	January	February	March	April	May	June	July
Alabama	483, 200	435, 100	484,000	468,000	479, 800	464, 200	474, 600
Colorado	55, 300	51, 400	56, 100	54,500	57, 200	56, 200	
Illinois	317, 300	289, 600	315, 100	306, 600	319, 200	308, 700	59, 200 316, 700
Indiana	625, 900	554,600	615, 400	588, 700	604, 400	580, 600	
Maryland	177, 600	158, 200	178, 000	171, 900	177, 500	172, 400	609, 100 176, 800
Massachusetts	101, 400	91, 100	99, 900	96, 800	101, 200		
Michigan	268, 300	243, 600	270, 200	261, 800	271, 300	96, 800	97, 900
Michigan Minnesota	79, 400	69, 700	77, 900			257, 900	263,000
New Jersey	91, 200	80, 800	88, 900	73, 700	78, 400	78,900	84,000
New York	448, 300	407, 900	448, 200	85, 100	89, 400	85, 100	87,000
Ohio	835, 900		831, 700	434, 700	448, 200	434, 700	440,600
Pennsylvania	1 226 700	758, 100		810, 300	835, 700	805, 900	836, 600
Tennessee	1, 000, 700	1, 209, 600	1, 348, 000	1, 299, 200	1, 356, 800	1, 325, 500	1, 385, 800
Utah	18, 300	17, 200	19, 300	18,000	19, 400	19,000	19, 500
West Virginia		16,600	21, 500	21, 100	21,600	20,900	21,000
West virginia	177, 800	162, 400	182, 200	183, 400	212, 300	209, 200	219, 200
Connecticut, Kentucky, Missouri, Rhode Island, and Wis-			1.54	1			
consin	193, 700	174, 400	194, 300	186, 600	193, 200	188, 600	191, 800
	5, 228, 900	4, 720, 300	5, 230, 700	5, 060, 400	5, 265, 600	5, 104, 600	5, 282, 800
At merchant plantsAt furnace plants	1, 259, 300 3, 969, 600	1, 142, 000 3, 578, 300	1, 268, 300 3, 962, 400	1, 226, 200 3, 834, 200	1, 280, 300 3, 985, 300	1, 246, 200 3, 858, 400	1, 286, 400 3, 996, 400
At merchant plantsAt furnace plants	1, 259, 300 3, 969, 600				1, 280, 300 3, 985, 300 November		1, 286, 400 3, 996, 400 Total
State		3, 578, 300 August	Septem- ber	3, 834, 200 October	Novem- ber	3, 858, 400 Decem- ber	3, 996, 400 Total
State Alabama		August 470, 400	September 451, 900	3, 834, 200 October 462, 400	November 448, 500	December 457, 400	Total  5, 579, 500
State  Alabama Colorado		August 470, 400 59, 000	September  451, 900 56, 300	3, 834, 200 October 462, 400 57, 200	November 448, 500 56, 000	December 457, 400 57, 800	Total  5, 579, 500 676, 200
State  Alabama Colorado		August 470, 400 59,000 311, 100	September  451, 900 56, 300 297, 800	3, 834, 200 October 462, 400 57, 200 310, 900	November  448, 500 56, 000 297, 800	December 457, 400 57, 800 299, 300	3, 996, 400  Total  5, 579, 500 676, 200 3, 690, 100
State  Alabama Colorado Illinois Indiana		August  470, 400 59, 000 311, 100 625, 000	September  451, 900 56, 300 297, 800 619, 900	3, 834, 200 October 462, 400 57, 200 310, 900 634, 200	November 448, 500 56, 000 297, 800 615, 800	December 457, 400 57, 800 299, 300 663, 900	3, 996, 400  Total  5, 579, 500 676, 200 3, 690, 100 7, 337, 500
State  Alabama Colorado Illinois Indiana Maryland		August  470, 400 59, 000 311, 100 625, 000 177, 700	September  451, 900 56, 300 297, 800 619, 900 174, 500	3, 834, 200 October 462, 400 57, 200 310, 900 634, 200 180, 500	November 448, 500 56, 000 297, 800 615, 800	December 457, 400 57, 800 299, 300 663, 900 181, 500	5, 579, 500 676, 200 3, 690, 100 7, 337, 500 2, 103, 700
Alabama Colorado Illinois Indiana Maryland Massachusetts		August  470, 400 59,000 311,100 625,000 177,700 98,700	September  451, 900 56, 300 297, 800 619, 900 174, 500 97, 800	0ctober 462, 400 57, 200 310, 900 634, 200 180, 500 100, 800	November   448, 500   56,000   297, 800   615, 800   177, 100   95,700	3,858,400   December   457,400   57,800   299,300   663,900   181,500   98,300	Total  5, 579, 500 676, 200 3, 690, 100 7, 337, 500 2, 103, 700 1, 176, 400
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michican		470, 400 59, 000 311, 100 625, 000 177, 700 98, 700 264, 200	September  451, 900 56, 300 297, 800 619, 900 174, 500 97, 800 254, 600	3, 834, 200 October 462, 400 57, 200 310, 900 634, 200 100, 800 263, 200	3, 985, 300 November 448, 500 56, 000 297, 800 615, 800 177, 100 95, 700 256, 200	3, 858, 400  December  457, 400 57, 800 299, 300 663, 900 181, 500 98, 300 264, 800	5, 579, 500 676, 200 3, 690, 100 7, 337, 500 2, 103, 700 1, 176, 400 3, 139, 100
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota		August  470, 400 59,000 311,100 625,000 177,700 98,700 264,200 83,900	September  451, 900 56, 300 297, 800 174, 500 97, 800 254, 600 79, 600	0ctober 462, 400 57, 200 310, 900 634, 200 180, 500 100, 800 263, 200 83, 700	3,985,300   November   448,500   56,000   297,800   177,100   95,700   256,200   82,400	3, 858, 400  December  457, 400 57, 800 299, 300 181, 500 98, 300 264, 800 83, 700	5, 579, 500 676, 200 3, 690, 100 2, 103, 700 1, 176, 400 3, 139, 100 955, 300
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota New Jersey		470, 400 59,000 311, 100 625,000 177,700 264,200 83,900 86,200	3, 962, 400 September 451, 900 56, 300 297, 800 619, 900 174, 500 97, 800 254, 600 79, 600 85, 500	462, 400 57, 200 310, 900 634, 200 180, 500 100, 800 263, 200 83, 700 86, 200	3, 985, 300  November  448, 500 56, 000 297, 800 615, 800 177, 100 95, 700 256, 200 82, 400 85, 400	3, 858, 400  December  457, 400 57, 800 299, 300 663, 900 181, 500 98, 300 264, 800 83, 700 87, 700	Total  5, 579, 500 676, 200 3, 690, 100 7, 337, 500 2, 103, 700 1, 176, 400 3, 139, 100 955, 300 1, 038, 500
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota New Jersey New York		470, 400 59, 000 311, 100 625, 000 177, 700 98, 700 264, 200 83, 900 86, 200 430, 800	September  451, 900 56, 300 297, 800 619, 900 174, 500 97, 800 254, 600 79, 600 85, 500 414, 000	3, 834, 200 October 462, 400 57, 200 310, 900 100, 800 100, 800 263, 200 88, 200 88, 200 423, 000	3, 985, 300  November  448, 500 56, 000 297, 800 615, 800 95, 700 95, 200 82, 400 83, 400 420, 900	3,858,400   December   457,400   57,800   299,300   663,900   181,500   98,300   264,800   83,700   87,700   429,100	Total  5, 579, 500 676, 200 3, 690, 100 7, 337, 500 1, 176, 400 955, 300 1, 038, 500 5, 180, 400
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota New Jersey New York Ohio		470, 400 59,000 311, 100 625,000 177,700 98,700 264,200 430,800 98,48,200	September  451, 900 56, 300 297, 800 619, 900 174, 500 97, 800 254, 600 79, 600 85, 500 414, 000 824, 900	462, 400 57, 200 310, 900 634, 200 180, 500 100, 800 263, 200 423, 000 423, 000 86, 200 423, 000	3, 985, 300  November  448, 500 56, 000 297, 800 615, 800 177, 100 95, 700 256, 200 82, 400 420, 900 822, 800	457, 400 57, 800 299, 300 663, 900 181, 500 284, 800 264, 800 87, 700 429, 100 850, 200	5, 579, 500 676, 200 3, 690, 100 7, 337, 500 2, 103, 700 1, 176, 400 3, 139, 100 955, 300 1, 038, 500 5, 180, 400 9, 912, 800
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota New Jersey New York Ohio Pennsylvania		3, 578, 300  August  470, 400 59, 000 311, 100 625, 000 177, 700 98, 700 264, 200 83, 900 490, 800 490, 800 1, 412, 100	September  451, 900 56, 300 297, 800 174, 500 97, 800 254, 600 79, 600 414, 000 824, 900 1389, 000	3, 834, 200  October  462, 400 57, 200 310, 900 180, 500 1100, 800 263, 200 83, 700 86, 200 423, 000 86, 200 423, 000 884, 500 1, 425, 200	3,985,300  November  448,500 56,000 297,800 177,100 95,700 256,200 82,400 420,900 82,400 1,396,000	3, 858, 400  December  457, 400 57, 800 299, 300 181, 500 98, 300 264, 800 83, 700 429, 100 850, 200 1, 446, 300	7otal  5, 579, 500 676, 200 3, 690, 100 2, 103, 700 1, 176, 400 9, 955, 300 1, 98, 500 5, 180, 400 9, 912, 800 16, 310, 200
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota New Jersey New York Ohio Pennsylvania Tennessee		3, 578, 300  August  470, 400 59, 000 311, 100 625, 000 177, 700 264, 200 88, 900 86, 200 430, 800 846, 200 1, 412, 100 19, 400	3, 962, 400  September  451, 900 56, 300 297, 800 619, 900 174, 500 97, 800 254, 600 85, 500 414, 900 1, 369, 000 20, 500	3, 834, 200 October 462, 400 57, 200 310, 900 634, 200 180, 500 100, 800 263, 200 88, 200 423, 000 88, 200 1, 425, 200 1, 425, 200 21, 500	3,985,300  November  448,500 56,000 297,800 615,800 177,100 95,700 256,200 252,400 82,400 420,900 822,800 1,396,000 20,800	3, 858, 400  December  457, 400 57, 800 299, 300 663, 900 181, 500 98, 300 264, 800 87, 700 429, 100 850, 200 1, 446, 300 21, 600	5, 579, 500 676, 200 3, 690, 100 7, 337, 500 1, 176, 400 9, 15, 300 1, 038, 500 5, 180, 400 9, 912, 800 16, 310, 200 234, 500
State  Alabama Colorado Illinois Indiana. Maryland Massachusetts Michigan Minnesota New Jersey New York Ohio Pennsylvania Tennessee		3, 578, 300  August  470, 400 59, 000 311, 100 625, 000 177, 700 98, 700 264, 200 83, 900 430, 800 430, 800 1, 412, 100 19, 400 20, 000	3, 962, 400  September  451, 900 56, 300 297, 800 619, 900 77, 800 254, 600 79, 600 85, 500 414, 000 824, 900 1, 369, 000 20, 500 19, 600	3, 834, 200  October  462, 400 57, 200 310, 900 634, 200 180, 500 100, 800 263, 200 423, 200 423, 000 844, 500 1, 425, 200 21, 500 21, 100	3,985,300  November  448,500 56,000 297,800 177,100 95,700 256,200 82,400 420,900 420,900 1,396,000 20,800 11,396,000 11,990	3, 858, 400  December  457, 400 57, 800 299, 300 98, 300 264, 800 83, 700 429, 100 850, 200 1, 446, 300 21, 600	Total  5, 579, 500 676, 200 3, 690, 100 7, 337, 550 2, 103, 700 1, 176, 400 3, 139, 100 955, 300 1, 038, 500 5, 180, 400 9, 912, 800 234, 500 234, 500 242, 500
State  Alabama Colorado Illinois Indiana. Maryland Massachusetts Michigan Minnesota New Jersey New York Ohio Pennsylvania Tennessee Utah West Virginia		3, 578, 300  August  470, 400 59, 000 311, 100 625, 000 177, 700 264, 200 88, 900 86, 200 430, 800 846, 200 1, 412, 100 19, 400	3, 962, 400  September  451, 900 56, 300 297, 800 619, 900 174, 500 97, 800 254, 600 85, 500 414, 900 1, 369, 000 20, 500	3, 834, 200 October 462, 400 57, 200 310, 900 634, 200 180, 500 100, 800 263, 200 88, 200 423, 000 88, 200 1, 425, 200 1, 425, 200 21, 500	3,985,300  November  448,500 56,000 297,800 615,800 177,100 95,700 256,200 252,400 82,400 420,900 822,800 1,396,000 20,800	3, 858, 400  December  457, 400 57, 800 299, 300 663, 900 181, 500 98, 300 264, 800 87, 700 429, 100 850, 200 1, 446, 300 21, 600	Total  5, 579, 500 676, 200 3, 690, 100 7, 337, 550 2, 103, 700 1, 176, 400 3, 139, 100 955, 300 1, 038, 500 5, 180, 400 9, 912, 800 234, 500 234, 500 242, 500
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota New Jersey New York Ohio Pennsylvania Temnessee Utah West Virginia Connecticut, Kentucky, Misson	ri. Rhode	3, 578, 300  August  470, 400 59, 000 311, 100 625, 000 177, 700 98, 700 264, 200 83, 900 430, 800 430, 800 1, 412, 100 19, 400 20, 000 224, 100	3, 962, 400  September  451, 900 56, 300 297, 800 619, 900 174, 500 97, 800 254, 600 79, 600 255, 500 414, 000 824, 900 10, 600 20, 500 216, 500	3, 834, 200  October  462, 400 57, 200 310, 900 684, 200 180, 500 100, 800 263, 200 83, 700 83, 700 21, 500 21, 100 225, 400	3,985,300  November  448,500 56,000 297,800 615,800 177,100 95,700 256,200 82,400 83,400 420,900 420,900 1,396,000 20,800 19,900 213,300	3, 858, 400  December  457, 400 57, 800 299, 300 663, 900 181, 500 98, 300 264, 800 87, 700 429, 100 21, 600 21, 600 218, 600	5, 579, 500 676, 200 3, 690, 100 7, 337, 500 2, 103, 700 1, 176, 400 955, 300 1, 038, 500 9, 912, 800 16, 310, 200 234, 500 242, 500 2, 444, 400
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota New Jersey New York Ohio Pennsylvania Trennessee Utah West Virginia	ri. Rhode	3, 578, 300  August  470, 400 59, 000 311, 100 625, 000 177, 770 264, 200 83, 900 84, 200 430, 800 846, 200 1, 412, 100 20, 000 224, 100 191, 200	3, 962, 400  September  451, 900 56, 300 297, 800 619, 900 174, 500 97, 800 85, 500 414, 000 824, 900 10, 600 216, 500 186, 000	3, 834, 200  October  462, 400 57, 200 310, 900 634, 200 180, 500 100, 800 263, 200 83, 700 84, 200 423, 000 84, 200 21, 100 225, 400 194, 000	3,985,300  November  448,500 56,000 297,800 615,800 177,100 95,700 256,200 82,400 82,400 822,800 1,396,000 20,800 19,900 213,300 187,400	3, 858, 400  December  457, 400 57, 800 299, 300 663, 900 181, 500 98, 300 264, 800 83, 700 429, 100 20, 600 21, 446, 300 20, 600 218, 600 192, 600	5, 579, 500 676, 200 3, 690, 100 7, 337, 500 2, 103, 700 1, 176, 400 3, 139, 100 9, 51, 80, 400 1, 935, 300 1, 334, 500 2, 444, 400 2, 273, 800
State  Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota New Jersey New York Ohio Pennsylvania Tennessee Utah West Virginia Connecticut, Kentucky, Misson	ri, Rhode	3, 578, 300  August  470, 400 59, 000 311, 100 625, 000 177, 700 98, 700 264, 200 83, 900 430, 800 430, 800 1, 412, 100 19, 400 20, 000 224, 100	3, 962, 400  September  451, 900 56, 300 297, 800 619, 900 174, 500 97, 800 254, 600 79, 600 255, 500 414, 000 824, 900 10, 600 20, 500 216, 500	3, 834, 200  October  462, 400 57, 200 310, 900 684, 200 180, 500 100, 800 263, 200 83, 700 83, 700 21, 500 21, 100 225, 400	3,985,300  November  448,500 56,000 297,800 615,800 177,100 95,700 256,200 82,400 83,400 420,900 420,900 1,396,000 20,800 19,900 213,300	3, 858, 400  December  457, 400 57, 800 299, 300 663, 900 181, 500 98, 300 264, 800 87, 700 429, 100 21, 600 21, 600 218, 600	Total  5, 579, 500 676, 200 3, 690, 100 2, 103, 700 1, 176, 400 3, 139, 100 955, 300 1, 038, 500 5, 180, 400 234, 500 242, 500

Table 6.—Beehive coke produced in the United States in 1942, by weeks [Estimated from railroad shipments]

		[250maccu nom ramoac	i surpments	·	
Week ended—	Week ended— Net tons		Net tons	Net tons Week ended—	
January 3	1 67, 400 141, 900 145, 600 152, 700 162, 700 158, 000 168, 600 147, 500 164, 200 158, 900 138, 900	May 9	151, 300 176, 100 186, 400 153, 100 155, 700 156, 500 179, 900 179, 800 132, 200 162, 100 155, 900	September 12	167, 900 173, 400 166, 600 161, 400 165, 100 167, 200 160, 700 149, 100 170, 400
21 28 April 4 11 18 25 May 2	161, 700 155, 700	25	159, 700 162, 400 157, 300 142, 500 157, 200 158, 800 169, 100	28	161, 100

<sup>13</sup> days only. 25 days only.

というなるとは書きてはないなられて

Table 7.—Beehive coke produced in the United States in 1942, by months and States in net tons

[Based upon reports from producers]

	[Dasca	ipon reperts from producere,						
State		January	February	March	April	Мау	June	
Alabama Colorado and Utah Kentucky and Tennessee Pennsylvania Virginia West Virginia		13, 300 8, 500 5, 200 594, 800 29, 200 24, 400	12, 100 7, 100 3, 400 560, 900 27, 500 24, 500	13, 200 8, 900 8, 400 616, 800 31, 600 15, 500	12, 900 9, 100 8, 000 602, 400 29, 300 24, 900	11, 400 7, 200 7, 500 619, 400 28, 400 26, 300	4,700 9,300 7,500 639,100 29,500 28,900	
		675, 400	635, 500	694, 400	686, 600	700, 200	719,000	
State	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total	
Alabama. Colorado and Utah. Kentucky and Tennessee. Pennsylvania Virginia. West Virginia.	5, 100 8, 800 7, 400 613, 000 29, 500 29, 000	4,600 9,600 6,100 613,900 30,100 32,400	4, 700 10, 500 4, 600 616, 400 29, 600 31, 800	4,800 10,800 5,000 639,400 28,900 33,200	4, 200 9, 800 5, 600 587, 600 28, 300 31, 900	4, 400 10, 200 5, 000 605, 700 28, 600 32, 400	95, 400 109, 800 73, 700 7, 309, 400 350, 500 335, 200	
	692, 800	696,700	697, 600	722, 100	667, 400	686, 300	8, 274, 000	

# PRODUCTION BY FURNACE AND NONFURNACE PLANTS

Tables 8 and 9 give the production of byproduct coke by plants

associated with iron furnaces and by other plants.

The terms "furnace" and "merchant" plants originated in the Connellsville beehive-coke trade. In this report the distinction is applied to byproduct plants only. A "furnace" plant is defined as one that produces, primarily, furnace coke and has an assured outlet for this coke either through financial affiliations with or direct ownership by an iron works or through long-time contracts. The class of "other plants" includes a few plants that are affiliated with local iron furnaces but produce much more coke than the furnaces can absorb and therefore depend chiefly on the foundry and domestic trade or on merchant sales of furnace coke for disposal of the output. The classification of "other plants" also includes merchant producers of furnace coke who sell their entire output on the open market, plants affiliated with alkali works, low-temperature carbonization plants, plants that operate as gas utilities, and a number of plants that, although not public utilities, were constructed primarily to supply city gas and to sell their coke for domestic, industrial, or metallurgical uses. Because of the miscellaneous character of this group of plants, they are not designated as "merchant" but as "nonfurnace" or "other plants." From time to time it may be necessary to change the classification of a given plant because of a change in ownership or market connections.

The activity of "furnace plants" depends principally on the activity of the iron and steel industry, therefore the output of furnace coke follows closely the trend of that industry. In 1942 furnace plants contributed 76 percent of the total byproduct-coke output compared with 77 percent in 1941 and 77 percent in 1940. The relative proportions of "furnace" and "nonfurnace" coke have been remarkably constant during the past 3 years. The relative constancy of this production ratio between the two types of plants illustrates that the demands of industries other than the iron and steel industry affect the market sufficiently for the output of the nonfurnace group to follow, in general, the pattern established by the furnace group.

Table 8.—Number and production of byproduct-coke plants connected with iron furnaces and of other byproduct plants in the United States, 1913, 1918, and 1940-42

Year	Number of active plants		Coke produced (net tons)		Percent of production	
100	Furnace plants	Other plants	Furnace plants	Other plants	Furnace plants	Other plants
1913	20 36 45 45 46	16 24 40 42 42	9, 277, 832 19, 220, 342 41, 465, 177 44, 987, 913 47, 160, 043	3, 436, 868 6, 777, 238 12, 549, 132 13, 494, 509 15, 134, 866	73. 0 73. 9 76. 8 76. 9 75. 7	27. 0 26. 1 23. 2 23. 1 24. 3

Table 9.—Monthly and average daily production of byproduct coke by plants associated with iron furnaces and by all other plants in the United States, 1940-42, in net tons

Month	19	40	19	41	1942		
	Furnace plants	Other plants	Furnace plants	Other plants	Furnace plants	Other plants	
Monthly production:							
January February March April May June July	3, 644, 300	1, 076, 300	3, 825, 200	1, 113, 600	3, 969, 600	1, 259, 300	
February	3, 038, 200	990, 100	3, 468, 200	1,039,200	3, 578, 300	1, 142, 00	
Moreh	3, 082, 700	1, 053, 900	3, 850, 400	1, 154, 800	3, 962, 400	1, 268, 30	
April	2, 985, 700	1,010,100	3, 423, 700	1,055,900	3, 834, 200	1, 226, 20	
Mon	3, 248, 200	1,007,800	3, 731, 800	1, 119, 800	3, 985, 300	1, 280, 30	
Terms	3, 395, 800	991, 400	3, 728, 500	1, 113, 200	3, 858, 400		
Juile	2, 590, 600		9, 120, 000	1, 113, 200		1, 246, 20	
July	3, 599, 800	1,032,600	3, 875, 600		3, 996, 400	1, 286, 40	
August September	3, 658, 800	1,036,700	3, 875, 500	1, 143, 400	4,030,700	1, 289, 30	
September	3, 596, 900	1,043,800	3, 708, 400	1, 103, 000	3, 912, 000	1, 256, 40	
October	3, 750, 800	1, 102, 800	3, 827, 900	1, 148, 600	4,049,400	1, 294, 40	
November	3, 674, 700	1,088,800	3, 694, 800	1, 144, 400	3, 917, 400	1, 278, 60	
December	3, 789, 300	1, 114, 800	3, 977, 900	1, 214, 600	4, 065, 900	1, 307, 50	
	41, 465, 200	12, 549, 100	44, 987, 900	13, 494, 500	47, 160, 000	15, 134, 90	
verage daily production:		04 500	400 400	<b>0.</b> 000			
January	117, 600	34, 700	123, 400	35, 900	128, 100	40,60	
February	104,800	34, 100	123, 900	37, 100	127,800	40, 80	
March	99, 400	34,000	124, 200	37, 300	127, 800	40, 90	
April	99, 500	33, 700	114, 100	35, 200	127,800	40, 90	
May		32,500	120, 400	36, 100	128,600	41, 30	
June	113, 200	33,000	124, 300	37, 100	128, 600	41, 60	
July	116, 100	33, 300	125,000	36,900	128, 900	41, 50	
August	118,000	33, 500	125,000	36,900	130,000	41, 60	
September	119, 900	34,800	123,600	36,800	130, 400	41, 90	
October	121,000	35,600	123, 500	37,000	130, 600	41, 80	
November	122, 500	36, 300	123, 200	38, 100	130, 600	42, 60	
December	122, 200	36,000	128, 300	39, 200	131, 100	42, 20	
Average	113, 300	34, 300	123, 200	37,000	129, 200	41, 50	

### PRODUCTION BY STATES AND DISTRICTS

The intense activity in the coke industry during 1942 resulted in an increased output in 19 of the 20 States that produced byproduct coke. The average increase for the industry as a whole was 7 percent over the 1941 figure. The only State that did not increase its 1942 output was Indiana, because of the inactivity of 140 ovens at Gary, which were undergoing major repairs. These rebuilt ovens were completed and placed in operation by December 1942.

Pennsylvania led all States in the output of byproduct coke, and its 16,310,167 tons represented 26 percent of the total United States production. This was an increase of 677,813 tons (4 percent) over the output in 1941 and 5,315,913 tons (48 percent) over 1939. The statis-

tics of coke production alone fail to do justice to the importance of this State in the coke industry for, in addition to coke, it supplies much of the raw coal required by the byproduct ovens in adjoining States.

Compared with 1941 Alabama led all States in increased tonnage production of byproduct coke, with 819,649 tons, followed by Pennsylvania with 677,813 tons, Ohio with 628,589, and West Virginia with The States that showed the largest percentage of in-460.749 tons. crease were Tennessee with 111 percent, Minnesota with 39 percent, West Virginia with 23 percent, and Maryland with 20 percent over the 1941 output.

The production of beehive coke in 1942 was 8,274,035 tons, of which 7,309,337 tons (88 percent) were produced in Pennsylvania; Virginia and West Virginia each contributed 4 percent. All States that produced beehive coke in 1941, except Kentucky, increased their output in 1942. The State showing the greatest increase was Utah, with 119 percent, followed in order by Tennessee 86 percent, West Virginia 28

percent, and Pennsylvania 24 percent.

Table 10.—Byproduct and beehive coke produced in the United States, 1918 and 1939-42, by States, in net tons

[Exclusive of screenings or breeze]

State	1918	1939	1940	1941	1942
Byproduct:					
Alabama	2, 634, 451	3, 854, 505	4, 727, 378	4, 759, 862	5, 579, 511
Colorado	230, 663	398, 033	543, 548	622, 807	676, 209
Connecticut		(1)	(1)	(1)	(1)
Illinois	2, 285, 610	1, 884, 240	3, 014. 840	3, 660, 878	3, 690, 155
Indiana	3, 898, 215	4, 878, 033	6, 412, 716	7, 406, 724	7, 337, 512
Kentucky	517, 749	₹ · (1)	(1)	(1)	(1)
Maryland	474, 368	1, 578, 973	1,682 701	1, 752, 538	2, 103, 664
Massachusetts	556, 397	1, 057, 158	1, 130, 311	1, 161, 732	1, 176, 359
Michigan	(1)	2, 430, 688	2, 872, 026	2, 863, 563	3, 139, 137
Minnesota	784, 065	497, 079	524, 360	685, 873	955, 301
Missouri		(1)	(1)	(1)	(1)
New Jersey	682, 148	1, 003, 197	1,016,481	1, 031, 569	1. 038. 461
New York		4, 468, 437	5, 080, 403	5, 116, 308	5, 180, 384
Ohio	5, 226, 334	6, 135, +49	7, 897, 929	9, 284, 194	9, 912, 783
Pennsylvania	4, 586, 981	10, 994, 254	14, 861, 657	15, 632, 354	16, 310, 167
Rhode Island	-,000,00-	(1)	(1)	(1)	(1)
Tennessee		79, 448	94, 454	1ìí, 310	234, 529
Utah		189, 194	218, 949	236, 607	242, 531
Washington		100. 20-	210,010	200,000	, 00
West Virginia		1, 598, 198	1, 899, 849	1, 983, 619	2, 444, 368
Wisconsin		1, 000, 100	1,000,010	1, 000, 010	7,113,000
Combined States	2, 293, 021	1, 834, 927	2, 036, 707	2, 172, 484	2, 273, 838
Combined States	2, 293, 021	1,004,021	2,000,101	2, 1/2, 303	2, 210, 600
	25, 997, 580	42, 882, 313	54, 014, 309	58, 482, 422	62, 294, 909
Beehive:					
Alabama	1,717,721			95, 200	95, 428
Colorado		56, 836	62, 417	80, 196	87, 447
Georgia		00,000	0_,	00,200	
Kentucky			(1)	2,054	1, 138
New Mexico				_, -,	
Ohio					
Oklahoma					
Pennsylvania	22, 136, 664	1, 125, 971	2, 550, 367	5, 891, 118	7, 309, 337
Tennessee	302, 637	1, 120, 0, 1	5, 251	39, 083	72, 541
Utah	- 302,007	8, 332	7, 398	16, 244	22, 402
		165, 317	198, 379	324, 573	350, 521
Virginia	1,234,230	100, 511	(1)	324,010	000,021
Washington	93, 659	0# 079	233, 154	261, 688	335, 221
West Virginia		87, 872	255, 154	201,000	350, 221
Combined States	461, 393		809		
	30, 480, 792	1, 444, 328	3, 057, 825	6, 704, 156	8. 274, 035
Grand total	56, 478, 372	44, 326, 641	57, 072, 134	65, 186, 578	70, 568, 944

<sup>1</sup> Included under "Combined States."

Table 11.—Coke produced, value, number of ovens, coal charged, and average yield in 1942, by States [Exclusive of screenings or breeze]

8				Byprod	uct					Ве	ehive .			Т	otal
State	Plants	Ovens	Coal used	Yield of coke from	Coke pro-	Value of c		Ovens	Coal used		Coke pro-	Value of over		Coke pro-	Value of coke at
	Flants	Ovens.	(net tons)	coal (per- cent)	(net tons)	Total	Per ton	Ovens	(net tons)	coal (per- cent)	(net tons)	Total	Per ton	(net tons)	ovens
Alabama Colorado Illinois	8 1 9	1, 352 188 915	7, 780, 673 1, 020, 797 5, 224, 824	71.71 66.24 70.63	5, 579, 511 676, 209 3, 690, 155	\$26, 359, 204 (1) 27, 364, 122	\$4.72 (1) 7.42	394 260	155, 290 136, 905	61. 45 63. 87	95, 428 87, 447	\$591, 646 (1)	\$6. 20 (1)	5, 674, 939 763, 656 3, 690, 155	\$26, 950, 850 (1) 27, 364, 122
Indiana	5 1 2	1, 592 422 215	10, 147, 475 2, 904, 798 1, 668, 918	72. 31 72. 42 70. 49	7, 337, 512 2, 103, 664 1, 176, 359	52, 848, 043	7. 20 (1) (1) 6. 94							7, 337, 512 2, 103, 664 1, 176, 359	52, 848, 043
Michigan Minnesota New Jersey New York	7 3 2 8	641 196 228 1,054	4, 359, 802 1, 270, 855 1, 439, 043 7, 255, 819	72.00 75.17 72.16 71.40	3, 139, 137 955, 301 1, 038, 461 5, 180, 384	21, 793, 813 7, 507, 413 (1) 37, 660, 727	6. 94 7. 86 (1) 7. 27							3, 139, 137 955, 301 1, 038, 461 5, 180, 384 9, 912, 783	21, 793, 813 7, 507, 413 (1) 37, 660, 727
Ohio Pennsylvania Tennessee	15 14 1	1,963 3,417 44	13, 733, 261 23, 889, 180 329, 867	72. 18 68. 27 71. 10	9, 912, 783 16, 310, 167 234, 529	59, 087, 481 77, 293, 489	5. 96 4. 74	240	11, 292, 336 122, 940	59.01	72, 541	41, 263, 580	5. 65 (1) (1)	23, 619, 504 307, 070	37, 660, 727 59, 087, 481 118, 557, 069
Utah Virginia Washington	1	56	405, 128	59.87	242, 531	(1)	(1) (1)	297 753 160	43, 865 584, 620	51.07 59.96	22, 402 350, 521	2, 281, 289	6. 51	264, 933 350, 521	2, 281, 289
West Virginia Connecticut, Kentucky, Missouri, Rhode Is-	5	506	3, 502, 958	69. 78	2, 444, 368	9, 103, 440	3.72	1, 140	537, 959	62.31	335, 221	2,066,217	6. 16	2,779,589	11, 169, 657
land, and Wisconsin Undistributed	6	514	3, 040, 423	74. 79	2, 273, 838	17, 935, 380 41, 058, 855	7. 89 7. 50	14	1,897	60.00	1, 138	6, 225 1, 392, 820	5. 47 7. 64	2, 274, 976	42, 451, 675
Total: 1942	88 87	13, 303 13, 016	87, 973, 821 82, 608, 837	70.81 70.79	62, 294, 909 58, 482, 422	378, 011, 967 316, 477, 231	6. 07 5. 41		12, 875, 812 10, 529, 316	64. 26 63. 67		47, 601, 777 36, 490, 006	5. 75 5. 44	70, 568, 944 65, 186, 578	425, 613, 744 352, 967, 237

Included under "Undistributed."
 Number of ovens in existence at plants that operated in 1942 as reported by operators.

# NUMBER AND TYPE OF OVENS

Byproduct ovens.—At the end of 1942 there were 13,303 byproduct ovens of all types in the United States. This represented an addition of 287 ovens to the 13,016 reported at the end of 1941. The continued expansion of the iron and steel industry at the end of 1942 found the byproduct-coke producers busy replacing old ovens and building new batteries to meet the anticipated needs for metallurgical fuel. At the close of the year, 1,327 new ovens with an annual coke capacity of 6,775,000 tons were reported under construction. The number of byproduct ovens in the United States at the end of 1942, by types, is given in table 14, by States. The majority of the ovens in the byproduct-coke industry are of Koppers and Koppers-Becker types, and of the 13,303 in existence at the end of 1942, 10,263 (77 percent) were of these two types.

Beehive ovens.—The total ovens in existence, as reported by operators, dropped from 18,669 in 1941 to 16,295 in 1942. This change is not significant, however, as operators may consider certain ovens serviceable one year and not serviceable the next, according to general conditions. Some operators do not report any ovens in existence at plants operated by them that are not leased by them from the owners; as plants change management from time to time, different reports are received as to the total ovens in existence at the various plants at

various times.

Table 12.—Coke ovens completed and abandoned in the United States in 1942 and total number in existence at the end of year, by States

					Ovens			
State	Plants in exist- ence		ence Dec.	1	Vew	Aban-		onstruc- c. 31, 1942
State	Dec. 31, 1942	Num- ber	Annual capacity (net tons of coke)	Num- ber	Annual capacity (net tons of coke)	doned during year	Num- ber	Annual capacity (net tons of coke)
Byproduct: AlabamaCalifornia	8	1, 352	5, 770, 950				138 90	(1) (1)
Colorado	1 1 9 5	188 70 915 1, 592	645, 300 (1) 4, 099, 100 7, 999, 600	2 140	(1)		124 264	(¹) 1, 346, 000
Kentucky Maryland Massachusetts Michigan	1 1 2 7 3	120 422 215 641	2, 124, 000 1, 165, 880 3, 219, 658			19		
Minnesota Missouri New Jersey New York	1 2 8	196 64 228 1,054	966, 000 (1) 1, 033, 000 5, 507, 699			11	76 136	e) e)
Ohio Pennsylvania Rhode Island Tennessee	15 14 1 1	1, 963 3, 417 65 44	9, 411, 800 17, 129, 900 (1) (1)	201	1, 057, 500	106	105	
Texas Utah Washington West Virginia	15	56	238, 710 2, 681, 250	82	(1)		125 252 17	(1) (1) (1)
Wisconsin Undistributed	2	195	2, 562, 125		1, 269, 300	100	1 997	5, 429, 00 6, 775, 00
At merchant plants	88 42 46	3, 581 9, 722	64, 554, 972 15, 749, 788 48, 805, 184	423 62 361	2, 326, 800 308, 300 2, 018, 500	30 106		221, 00 6, 554, 00

See footnotes at end of table.

TABLE 12.—Coke ovens completed and abandoned in the United States in 1942 and total number in existence at end of year, by States-Continued

		50			Ovens			
	Plants in exist- ence		tence Dec. I, 1942		New	Aban- doned	Under construc- tion Dec. 31, 1942	
	Dec. 31, 1942	Num- ber	Annual capacity (net tons of coke)	Num- ber	Annual capacity (net tons of coke)	during year	Num- ber	Annual capacity (net tons of coke)
Beehive: Alabama Colorado Kentucky	4	394 260 14	231, 400			151		
Pennsylvania Tennessee	84 2	13, 037 240	8, 762, 625 85, 000			186		
Utah Virginia Washington	1 5 1	297 753 160	401, 074 (1)			520 553		
West Virginia Undistributed	9	1, 140	544, 500 383, 996			76		
	108	³ 16, 295	10, 408, 595			1, 486		

Table 13.—Average number of beehive ovens active in the United States in 1942, by months

Month	Number	Month	Number	Month	Number
January	12, 515	May	12, 797	September	12, 782
February	12, 516		12, 658	October	12, 780
March	12, 521		12, 741	November	12, 900
April	12, 680		12, 845	December	12, 834

Table 14.—Byproduct ovens of each type in the United States at end of 1942, b States

State	Koppers	Koppers Becker	Semet- Solvay	Wilputte	Cambria	American Foundation	All others 1	Total
Alabama Colorado Connecticut	459 116	413 72 70	420	60				1, 352 188
Illinois Indiana Kentucky	379 824	282 248	120 120 120	88 400			46	70 915 1,592 120
Maryland Massachusetts Michigan Minnesota	300	122 160 295 41	346	55				422 215 641 196
Missouri New Jersey New York	56 191 150	37 593	180	76		55	8	64 228 1,054
Ohio	1, 238 1, 550 40	356 1, 559 25	369 88	97	120		3	1, 963 3, 417 65
Utah	154 100	56 207 15	24 	20 145				44 56 506 195
	5, 712	4, 551	1,867	941	120	55	57	13, 303
At merchant plants At furnace plants	771 4, 941	1, 217 3, 334	1, 141 726	340 601	120	55	57	3, 581 9, 722

<sup>&</sup>lt;sup>1</sup> Includes 46 Curran-Knowles, 8 Pictte, and 3 Disco ovens in 1942.

Included under "Undistributed."
 Reconstructed ovens.
 Number of ovens in existence at plants that operated in 1942, as reported by operators.

### CAPACITY OF BYPRODUCT PLANTS

The potential maximum capacity of the 13,303 byproduct-coke ovens in existence at the end of 1942 was 176,863 tons a day and that of the 1,327 new ovens under construction at the end of the year 18,562 tons a day. Capacity, as thus stated, is defined as the total quantity of coke of the grade the operator aims to produce that can be obtained in a 24-hour period with all conditions favorable and all This capacity depends not only on the amount of coal ovens active. placed in the lovens but on many other factors, including the temperature that can be maintained in the walls of the ovens, which is limited by the character of the refractory materials of these walls; the character and quality of the coal charged; and the width of the Therefore, the potential maximum capacity of the oven chamber. ovens as estimated by the operators is subject to change from year to year according to changes in coking time, coal mixtures, or other variables.

Table 15 shows the relationship between the production of by-product coke and the potential maximum capacity for each month in 1929 and 1939-42. The operating ratio of the plants has fluctuated with the demand for coke, as noted in the continual rise from 1939, when plants operated at 68.9 percent of the potential maximum capacity, to the all-time high ratio of 96.9 percent in 1942. This figure was 5 percent higher than the hitherto all-time high performance of 1941 and is a credit to the operators, when it is known that more than 50 percent of the ovens in operation in 1942 were more than 20 years old. The 46 furnace plants operated at 97.5 percent and the 42 nonfurnace plants at 95.1 percent of their potential maximum capacity.

Table 15.—Relationship of production to potential maximum capacity <sup>1</sup> at byproductcoke plants in the United States, 1929 and 1939–42, by months, in percent

Month	1929	1939	1940	1941	1942	Month	1929	1939	1940	1941	1942
January February March April May June July	88. 6 91. 3 93. 0 92. 8 94. 0 93. 9 93. 0	62. 8 63. 5 64. 1 56. 2 44. 4 59. 2 64. 4	89. 2 81. 3 78. 1 78. 0 80. 4 85. 6 86. 1	92. 0 92. 9 93. 2 86. 4 90. 6 93. 3 93. 7	94.3 94.2 94.3 94.3 98.1 98.3 97.6	August	93. 6 91. 9 92. 3 89. 0 83. 1	70. 2 77. 2 86. 6 90. 3 89. 7 68. 9	87. 3 89. 2 90. 2 91. 5 91. 2	93. 4 91. 9 92. 0 92. 1 94. 8	98. 0 98. 4 98. 4 98. 9 98. 4

<sup>&</sup>lt;sup>1</sup> Capacity of all ovens in existence, whether active or idle, based upon maximum daily capacity times days in month.

# QUANTITY AND COST OF COAL CHARGED

The quantity of coal used in the manufacture of coke increased 8 percent in 1942 compared with 1941, but the percentage of the total output of bituminous coal carbonized remained about the same and represented 17 percent of the bituminous-coal production. The total quantity of coal used in making coke in 1942 was 100,849,600 tons, of which 87,973,800 tons (87 percent) were used in byproduct ovens and 12,875,800 tons (13 percent) in beehive ovens.

The average cost of the coal per ton laid down at the ovens was \$4.38 for byproduct plants and \$2.52 for beehive plants as against \$3.92 and \$2.33 in 1941. The total cost of coal used in the byproduct and beehive industry in the manufacture of coke was \$417,465,208 compared with \$348,072,043 in 1941 and represented an increase of

20 percent.

However, not all of this figure represented revenue to the coal producers; for most byproduct plants it included the freight rate from mine to ovens. The average cost of coal charged into byproduct ovens in 1942 ranged from \$2.92 in West Virginia to \$5.64 in Minnesota, where it includes freight rates from distant mines. The average cost of coal for beehive ovens is much less than that for byproduct ovens, as the former are usually built at or near the producing mines and therefore benefit from the savings in transportation charges. West Virginia, with an average cost of \$2.18 per ton, was low among the beehive-producing States, and the costs ranged to \$3.90 per ton for Colorado and Utah.

The prices of bituminous coal used in making coke in 1942 were governed by Office of Price Administration General Maximum Price Regulation 120, effective May 18, 1942. This regulation was based upon the price of October 1 to 15, 1941, and at the same time took into account the increased costs of production and allowed the producers a somewhat higher price for bituminous coal sold at mines or preparation plants than that during the base period.

Table 16.—Coal consumed in coke ovens in the United States, 1940-42, by months, in net tons

		1940			1941			1942	
Month	By- product	Bee- hive	Total	By- product	Bee- hive	Total	By- product	Bee- hive	Total
January February March April May June July August September October November December	6, 648, 600 5, 671, 400 5, 824, 900 5, 925, 900 6, 179, 500 6, 608, 300 6, 697, 900 6, 922, 500 6, 793, 800 6, 993, 900 76, 582, 800	254, 700 221, 600 167, 800 173, 900 252, 100 385, 700 464, 500 454, 300 606, 400 657, 700 773, 600	5, 926, 100 6, 046, 500 5, 795, 600 6, 168, 900 6, 431, 600 7, 162, 400 7, 073, 500 7, 451, 500 7, 767, 500	6, 408, 900 7, 116, 400 6, 367, 800 6, 832, 500 6, 816, 700 7, 067, 100 6, 775, 400 7, 010, 200 6, 814, 600 7, 310, 300	830, 600 979, 800 155, 600 894, 100 931, 900 955, 400 1, 008, 700 948, 300 1, 012, 400 878, 600 1, 073, 900	7, 239, 500 8, 096, 200 6, 523, 400 7, 726, 600 7, 748, 600 8, 022, 500 8, 076, 400 7, 723, 700 8, 022, 600 7, 693, 200 8, 384, 200	6, 681, 700 7, 405, 400 7, 164, 600 7, 125, 900 7, 199, 700 7, 451, 800 7, 504, 900 7, 590, 300 7, 538, 600 7, 330, 400 7, 579, 700	988, 700 1, 080, 700 1, 068, 900 1, 089, 700 1, 118, 300 1, 07, 900 1, 084, 100 1, 085, 700 1, 123, 700 1, 108, 300	7, 670, 400 8, 486, 100 8, 233, 500 8, 515, 600 8, 318, 900 8, 589, 900 8, 376, 900 8, 662, 300 8, 648, 900

Table 17.—Total quantity and value at ovens of coal used in manufacturing coke in the United States in 1942, by States

State	Coal used	Cost of	coal	Coal per to	on of coke
state	(net tons)	Total	Average	Net tons	Cost
Byproduct plants: Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota New Jersey New York Ohio Pennsylvania Tennessee Utah West Virginia Connectiont Connectiont Ventuely Miscouri	10, 147, 475 2, 904, 798 1, 668, 918 4, 359, 802 1, 270, 855	\$24, 323, 343 (1) 27, 594, 391 55, 770, 928 (1) 21, 247, 723 7, 168, 467 (38, 971, 369 60, 571, 869 82, 270, 214 (1) (1) 10, 230, 029	\$3. 13 (1) 5. 28 5. 50 (1) (1) 4. 87 5. 64 (1) 5. 37 4. 41 3. 44 (1) (1) (2. 92	1. 39 1. 51 1. 42 1. 38 1. 38 1. 42 1. 39 1. 33 1. 39 1. 40 1. 39 1. 46 1. 41 1. 67 1. 43	\$4. 35 (1) 7. 50 7. 59 (1) 6. 77 7. 50 (1) 7. 52 6. 13 5. 02 (1) (1) 4. 18
Connecticut, Kentucky, Missouri, Rhode Island, and Wisconsin	3, 040, 423	15, 768, 592	5. 19	1.34	6.

<sup>&</sup>lt;sup>1</sup> Included under "Undistributed."

Table 17.—Total quantity and value at ovens of coal used in manufacturing coke in the United States in 1942, by States—Continued

	Coal used	Cost of	coal	Coal per t	on of coke
State	(net tons)	Total	Average	Net tons	Cost
Byproduct plants—Continued. Undistributed.		\$41, 090, 272	\$5. 29		\$7.51
	87, 973, 821	385, 007, 197	4.38	1. 41	6. 18
At merchant plants At furnace plants	20, 944, 947 67, 028, 874	104, 288, 233 280, 718, 964	4. 98 4. 19	1. 38 1. 42	6. 87 5. 95
Beehive plants: Alabama Colorado and Utah Kentucky and Tennessee Pennsylvania. Viginia. West Virginia.	155, 290 180, 770 124, 837 11, 292, 336 584, 620 537, 959	402, 795 704, 603 369, 966 28, 368, 972 1, 437, 888 1, 173, 787	2. 59 3. 90 2. 96 2. 51 2. 46 2. 18	1. 63 1. 65 1. 69 1. 54 1. 67 1. 60	4. 22 6. 44 5. 00 3. 87 4. 11 3. 49
	12, 875, 812	32, 458, 011	2. 52	1. 56	3. 93

Table 18.—Average cost per net ton of coal charged into byproduct-coke ovens in the United States, 1929 and 1939-42, by States

State	1929	1939	1940	1941	1942	State	1929	1939	1940	1941	1942
AlabamaIllinois	\$2.49 4.29	\$2.39 4.55	\$2. 41 4. 57	\$2.79 4.92	\$3.13 5.28	Tennessee Washington	\$3.02 5.26	\$3. 50	\$3. 46	\$3.67	(1)
Indiana Massachusetts	4.61	4.68	4.72	5. 16	5.50	West Virginia	2. 41	2. 33	2.39	2.63	\$2.92
Michigan	4.29	4.08	3. 99	4.35	4.87	United States					
Minnesota New York	5.04 4.22	5. 49 4. 61	5. 16 4. 56	5. 19 4. 87	5.64 5.37	Cost of coal per	3.50	3.75	3.68	3. 92	4. 38
Ohio Pennsylvania	3. 31 2. 73	3. 81 2. 93	3.78 2.84	4. 13 2. 69	4.41 3.44	ton of coke	5.04	5. 36	5. 23	5, 53	6. 18
	2. 70	2. 30	2.04	2.05	0.44		100				

Bureau of Mines not at liberty to publish data.

### PREPARATION AND SOURCE OF COAL

Washed and unwashed.—The preparation of coal used in making coke is very important to many coke producers. Coals available for coke manufacture that contain an undue proportion of ash or sulfur are usually cleaned before being charged into ovens. Both pneumatic cleaning and wet-washing methods are employed. Some coal is cleaned or washed at the mines, and some byproduct-coke plants have washeries adjacent to the ovens. In 1942, 24 coke plants used coal that had been washed at mines, and 7 byproduct-coke plants charged into their ovens coal that was cleaned at the ovens. Table 19 shows the quantity of washed and unwashed coal consumed in the coke ovens of each State. Of the 87,973,821 tons of coal charged into byproduct ovens in 1942, 23,452,747 tons (27 percent) were washed, and in beehive ovens 1,824,619 tons (14 percent) were washed. Colorado and Tennessee all the coal used for byproduct-coke manufacture in 1942 was washed; also most of that used in Alabama and mined within the State and about half of that used in Pennsylvania.

Sources.—Sources of coking coals have been brought into sharper focus in 1942 because of the close relationship of the coke industry to the iron and steel industry.<sup>5</sup> Pennsylvania and West Virginia are the leading sources of coal used in byproduct-coke manufacture, and these two States supplied more than 75 percent of the bituminous coal so used in 1942. Of the 90,401,393 tons of coking coal purchased by byproduct-coke producers, Pennsylvania supplied 35,636,227 tons (39 percent), followed in order by West Virginia with 32,407,634 tons

<sup>&</sup>lt;sup>8</sup> Chapman, H. M., Coking Coals and Their Importance in Winning the War: Blast Furnace and Steel Plant, vol. 30, No. 12, December 1942, pp. 1378-1379.

(36 percent); Kentucky with 10,541,692 tons (12 percent); and Alabama with 7,980,529 tons (9 percent). Other States that supplied appreciable tonnages were Virginia, Colorado, Utah, Illinois, and Tennessee.

Blending coals.—Many operators of byproduct-coke ovens have found that mixing or blending various types of coking coals before charging into ovens will improve the quality of the coke and increase the yield per ton of coal. Operators agree in general that a mixture of low- and high-volatile coals attains this result. However, lowvolatile coals with many satisfactory coking qualities expand when coked, and their use alone would cause difficulty in discharging the coke from the oven and injure the byproduct-oven walls. For this reason, it is customary to mix such coals with high-volatile coals, which shrink when coked. This practice also permits the use of coals that have good coking qualities but have objectionable impurities such as high content of ash, sulfur, and phosphorus and for this reason could not be used as 100-percent charge into the ovens to produce coke to conform with specifications upon this basis. Thus, coal mixing, in addition to producing a superior coke, enables the coke industry to utilize coals that in an unmixed condition would not be suitable for coke manufacture.

In 1942, 64 of the 88 active byproduct plants purchased coal of different volatile content. Of these, 40 plants purchased high- and low-volatile coal; 20 plants high-, medium-, and low-volatile; and 4 plants high- and medium-volatile.

Of the 90,401,393 tons of coal purchased, 58,249,586 tons (65 percent) were high-volatile (32 percent and over volatile matter), 19,228,466 tons (21 percent) were low-volatile (14 to 22 percent volatile matter), and 12,923,341 tons (14 percent) were medium-volatile (23 to 31 percent volatile matter).

Table 19.—Washed and unwashed coal used in manufacturing coke in the United States in 1942, by States in which used, in net tons

State	Washed	Unwashed	Total
Byproduct plants:			
Alabama	6, 957, 574	823, 099	7, 780, 673
Colorado	1,020,797		1, 020, 797
Illinois	459, 184	4, 765, 640	5, 224, 824
Indiana		10, 147, 475	10, 147, 475
Maryland		2,904,798	2, 904, 798
Massachusetts		1,668,918	1, 668, 918
Michigan	199,040	4, 160, 762	4, 359, 802
Minnogoto	รล์ วกก	1, 214, 655	1, 270, 855
New Jersey		1, 439, 043	1, 439, 043
New York	728, 907	6, 526, 912	7, 255, 819
Ohio	2, 588, 105	11, 145, 156	13, 733, 261
Pennsylvania	9, 955, 917	13, 933, 263	23 880 180
Tennessee	329, 867	10, 500, 200	23, 889, 180 329, 867
Utah	525, 501	405, 128	405, 128
	1, 135, 206	2, 367, 752	3, 502, 958
West Virginia	1, 150, 200	2, 301, 132	0, 002, 900
Connecticut, Kentucky, Missouri, Rhode Island,	01.050	0.010.470	0.040.400
and Wisconsin	21,950	3, 018, 473	3, 040, 423
	23, 452, 747	64, 521, 074	87, 973, 821
At merchant plants	2, 137, 637	18, 807, 310	20, 944, 947
At furnace plants	21, 315, 110	45, 713, 764	67, 028, 874
At furnace plants	21, 310, 110	40,710,704	01,020,019
Beehive plants:			
Alabama	135, 418	19.872	155, 290
Colorado and Utah	136, 905	43, 865	180, 770
Kentucky and Tennessee	104, 041	20, 796	124, 837
Pennsylvania.	1, 448, 255	9, 844, 081	11, 292, 336
Virginia		584, 620	584, 620
West Virginia.		537, 959	537, 959
11 COU T 1181111C		001,000	001,000
	1, 824, 619	11,051,193	12, 875, 812

The second secon

Table 20.—Coal purchased for manufacture of byproduct coke in the United States in 1942, by fields of origin, in net tons

[Based upon detailed reports from each coke plant. Difference between these totals and those shown in tables 1, 11, 16, etc., is due to change in stock, loss of weight in handling, and the fact that these represent purchases during the year rather than actual consumption]

State and district where coal was produced	Total pur- chased	States where coal was consumed—in order of importance
Alabama	7, 980, 529	Alabama.
Colorado	930, 642	Colorado.
Georgia	17, 188	Tennessee.
Illinois	355, 687	Illinois and Indiana.
Indiana	80, 929	Illinois.
Kentucky, Eastern:	00, 020	Introdus.
Elkhorn (including Hazard)	2, 679, 567	Indiana, Ohio, Michigan, New York, Illinois, New Jersey, Minnesota, and Wisconsin.
Harlan	4, 232, 317	Indiana, Ohio, Illinois, Minnesota, Michigan, and New York.
Kenova-Thacker	1, 755, 991	Michigan, Ohio, Wisconsin, and Illinois.
Miscellaneous	1, 873, 817	Indiana, Illinois, and Ohio.
New Mexico		Colorado.
Pennsylvania:		
Central Pennsylvania:		
Medium-volatile	407, 148	New York and Maryland.
Low-volatile	2, 917, 834	Pennsylvania, New York, Ohio, and Minnesota.
Connellsville	17, 069, 335	Pennsylvania, Ohio, West Virginia, New York, Illinois,
		and New Jersey.
Freeport	1, 629, 956	West Timeinia Ohio Michigan and Now Vork
Pittsburgh	12, 559, 474	Pennsylvania, New York, Ohio, Michigan, Illinois, New Jersey, Wisconsin, and Connecticut. Pennsylvania, West Virginia, and New York.
11000011811	12,000, 212	New Jersey, Wisconsin, and Connecticut.
Somerset	544, 991	Pennsylvania, West Virginia, and New York.
Westmoreland	438, 866	Pennsylvania, Maryland, Minnesota, and Connecticut.
Miscellaneous		New York, Pennsylvania, and Missouri.
Tennessee	320, 500	Tennessee.
Utah		Utah.
Virginia	819, 340	Michigan, New Jersey, Ohio, New York, Massachusetts,
A HRITING	010,010	Illinois, and Pennsylvania.
West Virginia:		Immons, and I changi transa.
Coal and Coke	122, 137	Pennsylvania.
Kanawha-Logan		Ohio, Indiana, Massachusetts, Illinois, West Virginia,
	0, 002, 242	Kentucky, Michigan, Wisconsin, New York, Connecticut, Pennsylvania, New Jersey, Rhode Island, Missouri and Minnesota.
New River: High-volatile	1, 360, 890	New York, New Jersey, Pennsylvania, Massachusetts
mign-voistile	1,000,080	and Michigan.
Tom moletile (including	9 991 460	New York New Jersey Massachusetts, Michigan
Low-volatile (including Winding Gulf).	2, 281, 469	Maryland, Rhode Island, Ohio, Illinois, Wisconsin, Minnesota, West Virginia, and Kentucky.  Maryland, Pennsylvania, West Virginia, Ohio, Michi-
Northern		gan, and Illinois.
Pocahontas 1		Indiana, Ohio, Illinois, Michigan, Maryland, Pennsylvania, Minnesota, New York, Kentucky, Wisconsin, Missouri, Connecticut, Alabama, and West Virginia.
Webster-Gauley	460,044	New York, Pennsylvania, and New Jersey.
Williamson	292, 715	Ohio, Massachusetts, and Michigan.
	90, 401, 393	

Includes 703,995 tons of Pocahontas coal produced in Virginia.

Table 21.—Coal purchased for manufacture of byproduct coke in the United States in 1942, by States where produced and where consumed and by merchant and furnace plants, in net tons

						Co	al produce	d in—					
State where coal was consumed	Alabama	Colorado	Georgia	Illinois	Indiana	Kentucky	New Mexico	Pennsyl- vania	Tennes- see	Utah	Virginia	West Virginia	Total
Alabama: Merchant plants Furnace plants	1, 751, 407 6, 229, 122											112, 352 10, 023	1, 863, 759 6, 239, 145
Total Alabama Colorado: Furnace plant							214, 347					122, 375	8, 102, 904 1, 144, 989
Illinois: Merchant plantsFurnace plants				227, 197	80, 929	187, 107 1, 336, 112		69, 754 241, 311			13, 050	1, 729, 954 1, 469, 704	2, 227, 062 3, 128, 056
Total Illinois				227, 197	80, 929	1, 523, 219		311, 065			13, 050	3, 199, 658	5, 355, 118
Indiana: Merchant plantsFurnace plants				128, 490		4, 508, 928					703, 995	930, 090 4, 168, 831	930, 090 9, 510, 244
Total Indiana				128, 490		4, 508, 928		78, 864			703, 995 17, 823	5, 098, 921 2, 829, 938 1, 643, 635	10, 440, 334 2, 908, 802 1, 661, 458
Michigan: Merchant plants Furnace plants						202, 400 1, 420, 599		204, 809 203, 643			155, 104 243, 024	868, 346 1, 024, 228	1, 430, 659 2, 891, 494
Total Michigan						1, 622, 999		408, 452			398, 128	1, 892, 574	4, 322, 153
Minnesota: Merchant plants Furnace plants						55, 531 462, 951		65, 065				292, 470 390, 066	413, 066 853, 017
Total Minnesota New Jersey: Merchant plants						518, 482 101, 526		65, 065 69, 750			177, 812	682, 536 1, 173, 384	1, 266, 083 1, 522, 472
New York: Merchant plants Furnace plants						281, 887		2, 054, 540 2, 537, 877			98, 313	1, 828, 121 363, 006	4, 262, 861 2, 900, 883
Total New York						281, 887		4, 592, 417			98, 313	2, 191, 127	7, 163, 744
Ohio: Merchant plantsFurnace plants						1, 932, 710		6, 320, 353			107, 357 1, 595	1, 430, 704 4, 851, 591	1, 538, 061 13, 106, 249
Total Ohio						1, 932, 710		6, 320, 353			108, 952	6, 282, 295	14, 644, 310

Pennsylvania: Merchant plants Furnace plants								179, 349 21, 458, 862			5, 262	807, 672 1, 931, 317	987, 021 23, 395, 441
Total Pennsylvania								21, 638, 211			5, 262	2, 738, 989	24, 382, 462
Tennessee: Merchant plant Utah: Furnace plant			17, 188						320, 500	392, 683			337, 688 392, 683
West Virginia: Merchant plants Furnace plants								9, 350 2, 079, 460				1, 526, 334 1, 006	1, 535, 684 2, 080, 466
Total West Virginia								2, 088, 810				1, 527, 340	3, 616, 150
Connecticut, Kentucky, Missouri, Rhode Island, and Wisconsin: Merchant plants	ĺ					51, 941		63, 240				3, 024, 862	3, 140, 043
•	7, 980, 529	930, 642	17, 188	355, 687	80, 929	10, 541, 692	214, 347	35, 636, 227	320, 500	392, 683	1, 523, 335	32, 407, 634	90, 401, 393
At merchant plants	1, 751, 407 6, 229, 122	930, 642	17, 188	227, 197 128, 490	80, 929	880, 392 9, 661, 300	214, 347	2, 715, 857 32, 920, 370	320, 500	392, 683	569, 459 953, 876	15, 367, 924 17, 039, 710	21, 849, 924 68, 551, 469

Table 22.—Coal purchased for manufacture of byproduct coke in the United States in 1942, by States where consumed and by volatile content 1

	Low-vol	atile	Medium-	volatile	High-vol	atile	Total coal
State where coal was consumed	Net tons	Percent of total	Net tons	Percent of total	Net tons	Percent of total	purchased (net tons)
Alabama: Merchant plants Furnace plants	112, 352 10, 023	6. 0 . 2	1, 620, 092 6, 092, 661	86. 9 97. 6	131, 315 136, 461	7. 1 2. 2	1, 863, 759 6, 239, 145
Total Alabama Colorado: Furnace plant	122, 375	1.5	7, 712, 753	95. 2	267, 776 1, 144, 989	3. 3 100. 0	8, 102, 904 1, 144, 989
Illinois: Merchant plants Furnace plants	627, 312 1, 277, 946	28. 2 40. 9	976, 184	43.8	623, 566 1, 850, 110	28. 0 59. 1	2, 227, 062 3, 128, 056
Total Illinois	1, 905, 258	35.6	976, 184	18. 2	2, 473, 676	46. 2	5, 355, 118
Indiana: Merchant plants Furnace plants	397, 753 4, 168, 835	42. 8 43. 8	532, 337	57. 2	5, 341, 409	56. 2	930, 090 9, 510, 244
Total Indiana Maryland: Furnace plant Massachusetts: Merchant plants.	4, 566, 588 709, 839 338, 823	43. 7 24. 4 20. 4	532, 337 461, 844	5. 1 27. 8	5, 341, 409 2, 198, 963 860, 791	51. 2 75. 6 51. 8	10, 440, 334 2, 908, 802 1, 661, 458
Michigan: Merchant plants Furnace plants	436, 677 652, 512	30. 5 22. 6			993, 982 2, 238, 982	69. 5 77. 4	1, 430, 659 2, 891, 494
Total Michigan	1, 089, 189	25. 2			3, 232, 964	74.8	4, 322, 153
Minnesota: Merchant plants	108, 456 390, 066	26. 3 45. 7	52, 773	12.8	251, 837 462, 951	60. 9 54. 3	413, 066 853, 017
Total Minnesota New Jersey: Merchant plants	498, 522 346, 153	39. 4 22. 7	52, 773	4.2	714, 788 1, 176, 319	56. 4 77. 3	1, 266, 083 1, 522, 472
New York: Merchant plants	608, 738 610, 736	14. 3 21. 1	743, 433 503, 595	17. 4 17. 4	2, 910, 690 1, 786, 552	68.3 61.5	4, 262, 861 2, 900, 883
Total New York	1, 219, 474	17.0	1, 247, 028	17.4	4, 697, 242	65. 6	7, 163, 744
Ohio: Merchant plantsFurnace plants	462, 025 3, 802, 710	30. 0 29. 0	245, 720 905, 830	16. 0 6. 9	830, 316 8, 397, 709	54. 0 64. 1	1, 538, 061 13, 106, 249
Total Ohio		29. 1	1, 151, 550	7.9	9, 228, 025	63.0	14, 644, 310
Pennsylvania: Merchant plants Furnace plants	187, 559 2, 808, 851	19. 0 12. 0	203, 341 24, 625	20.6	596, 121 20, 561, 965	60. 4 87. 9	987, 021 23, 395, 441
Total Penn- sylvania Tennessee: Merchant plant Utah: Furnace plant		12.3	227, 966 337, 688	100.0	21, 158, 086 392, 683	86. 8	24, 382, 463 337, 688 392, 683
West Virginia: Merchant plants Furnace plants	77, 708 183, 724	5. 1 8. 8	9, 350	.6	1, 448, 626 1, 896, 742	94. 3 91. 2	1, 535, 684 2, 080, 460
Total West Virginia Connecticut, Kentucky, Mis- souri, Rhode Island, and	261, 432	7. 2	9, 350	.3	3, 345, 368	92. 5	3, 616, 15
Wisconsin: Merchant plants	909, 668	29.0	213, 868	6.8	2, 016, 507	64. 2	3, 140, 04
£	19, 228, 466	21.3	12, 923, 341	14.3	58, 249, 586	64. 4	90, 401, 39
At merchant plantsAt furnace plants	4, 613, 224	21. 1 21. 3			11, 840, 070 46, 409, 516		

<sup>&</sup>lt;sup>1</sup> Low-volatile coals range from 14 to 22 percent volatile matter; medium-volatile, from 23 to 31 percent; and high-volatile, 32 percent and over.

# YIELD OF COKE PER TON OF COAL

Table 23.—Yield of coke from coal in byproduct and beehive ovens in the United States, 1939-42, by States, in percent

	19	39	19	40	19	41	19	42
State	Byprod- uct	Beehive	Byprod- uct	Beehive	Byprod- uct	Beehive	Byprod- uct	Beehive
AlabamaColoradoIllinois	71. 01 66. 03 68. 12	65, 41	71. 03 63. 95 70. 56	65. 20	71. 51 65. 13 71. 20	60. 66 64. 57	71. 71 66. 24 70. 63	61. 45 63. 87
Indiana Maryland Massachusetts Michigan	70. 26 72. 88 70. 72 69. 34		73. 24 72. 33 71. 11 70. 06		73. 31 72. 60 70. 36 71. 31		72.31 72.42 70.49 72.00	
Minnesota New Jersey New York	69. 92 71. 05 71. 16 71. 09		70. 50 71. 67 71. 34 71. 48		72. 13 71. 65 71. 39 71. 64		75. 17 72. 16 71. 40 72. 18	
Ohio Pennsylvania Tennessee Utah	68. 71 73. 00 58. 38	63. 42	68. 43 70. 51 59. 31	63. 80 59. 55 50. 89	68. 41 71. 94 59. 58	64. 06 59. 19 50. 95	68. 27 71. 10 59. 87	64. 78 59. 01 51. 07
Virginia Washington West Virginia	68. 12	56. 87 67. 04	69. 05	59. 97 60. 20 65. 79	69. 07	60. 02 62. 09	69.78	59. 96 62. 3
United States average	70. 05	62. 86	70. 53	63. 66	70. 79	63. 67	70.81	64. 20

COKE BREEZE Table 24.—Coke breeze recovered at coke plants in the United States in 1942, by States

		* ***			Used by	producer					
State	Yield per ton of coal (per- cent) 1	Prod	luced	For stear	n raising	For other p	urpeses, in- vater gas	So	ld	Wasted (net tons)	On hand Dec. 31 (net tons)
		Net tons	Value	Net tons	Value	Net tons	Value	Net tons	Value		
Byproduct ovens: Alabama. Colorado. Illinois. Indiana. Maryland Massachusetts. Michigan Minnesota. New Jersey New York Ohio. Pennsylvania.	4. 86 9. 94 6. 14 4. 75 6. 52 4. 60 4. 51 6. 24 4. 51 5. 08	377, 837 101, 508 321, 018 478, 933 133, 417 108, 766 200, 384 57, 294 89, 848 327, 095 697, 708 1, 392, 107	\$957,090 (2) 749,344 940,450 (2) 1,022,181 201,276 (2) 1,057,510 1,551,357 2,402,815	153, 275 27, 768 169, 974 273, 627 79, 698 100, 113 135, 913 24, 830 89, 050 255, 733 439, 711 1, 183, 130	\$290, 886 (2) 416, 585 558, 728 (2) 739, 800 73, 672 (2) 691, 531 931, 565 2, 043, 503	44, 398 16, 597 29, 461 124, 021 28, 233 4, 901 12, 632 5, 259 49, 550 157, 613 59, 010 3, 553	\$101, 175 (2) 60, 453 240, 895 (2) (2) 43, 676 21, 891 249, 643 340, 863 91, 191	146, 744 56, 592 130, 469 106, 119 29, 190 3, 877 49, 267 24, 033 54, 762 102, 988 126, 395	\$488, 890 (2) 313, 645 180, 800 (7) (2) 220, 506 88, 168 (2) 219, 189 224, 895 227, 832	2, 261	61, 840 711 73, 119 26, 815 81, 464 5, 521 35, 791 21, 633 1, 982 79, 829 148, 144
Tennessee Utah West Virginia Connecticut, Kentucky, Missouri, Rhode Island, and Wisconsin	4. 29 5. 29 4. 90 5. 22	21, 421 119, 707 158, 845	(2) (2) 252, 193 532, 333	87, 162 103, 082	166, 571 336, 615	6, 043 15, 163	(2) (2) 25, 725 559	9, 492 22, 127 27, 252 42, 282	(2) (2) 79, 175 156, 990		1, 525 686 11, 550 24, 804
Undistributed			1, 230, 572		758, 683		126, 794		355, 895		
Total byproduct, 1942	5.30	4,600,030	10, 897, 121	3, 123, 066	7, 008, 139	ò56, 690	1, 302, 865	932, 122	2, 555, 985	2, 261	655, 175
At merchant plants At furnace plants	5, 31 5, 29	1,050,991 3,549,039	3, 304, 187 7, 592, 934	674, 571 2, 448, 495	1, 898, 581 5, 109, 558	52, 709 503, 981	239, 753 1, 063, 112	309, 150 622, 972	1,077,621 1,478,364	2, 261	166, 443 488, 732
Total byproduct, 1941	5. 41	4, 432, 864	9, 530, 433	3, 335, 705	6, 962, 011	428, 058	882, 146	836, 159	2, 014, 560	2, 505	443, 366
Beehive ovens: Alabama. Colorado and Utah Kentucky and Tennessee.	5, 34 3, 29	8, 126 5, 952	12, 547 6, 655	7, 397	11, 673	5, 542	6, 040	729 2, 493	874 3, 738		102
Pennsylvania Virginia West Virginia	2.60 .22 1.30	131, 540 803 5, 232	121, 209 4, 050 6, 749	22, 632	28, 471	55 144	102 837	58,000 659 356	49, 916 3, 213 459	47, 258 4, 876	4, 834 20
Total beehive, 1942	2. 46	151, 653	151, 210	30, 029	40, 144	5, 741	6, 979	62, 237	58, 200	<sup>8</sup> 52, 134	4, 956

Yield computed by dividing production of breeze by coal charged at plants actually recovering.
 Included under "Undistributed."
 As reported; quantity produced but not used was undoubtedly greater. See Mineral Resources of the United States, 1922, part 2, pp. 726-727.

Control of the second

## CONSUMPTION OF COKE

The indicated consumption of coke in the United States in 1942 was 70,107,181 net tons—an 8-percent increase over the 1941 figure. Unusually heavy requirements resulted in the consumption of 54,694,746 tons of furnace coke. This tonnage represented 78 percent of the total requirements; and the remainder—22 percent—was used in foundries, in smelting the nonferrous metals, in the manufacture of water gas, in miscellaneous industries as a chemical reagent,

and in domestic heating.

Table 26 shows the coke and coking coal consumed per net ton of pig iron produced in the United States in 1913, 1918, and 1939—42. There was an increase in the 1942 consumption ratio of coke to pig iron, and the coke consumed per ton of pig iron and ferromanganese produced rose from 1,767.8 pounds in 1941 to 1,822.8 pounds in 1942—an increase of 55 pounds (3 percent). Because of this increase, it is indicated that the additional coke required to supply the needs of blast furnaces in 1942 amounted to approximately 1,800,000 tons more than if the furnaces had operated at the 1941 rate of coke consumption per ton of furnace output.

Table 25.—Coke consumed in manufacture of pig iron and for other purposes in the United States, 1913, 1918, and 1939–42, in net tons

Year	Total pro-	Imports	Exports	Net change in	Indicated United States	Consumed t		Remainde consumed other way		
				stocks	consump- tion 1	Quantity	Per- cent	Quantity	Per- cent	
1913 1918 1939 1940 1941 1942	46, 299, 530 56, 478, 372 44, 326, 641 57, 072, 134 65, 186, 578 70, 568, 944	101, 212 30, 168 141, 911 112, 550 267, 886 108, 782	987, 395 1, 687, 824 589, 925 804, 095 708, 971 839, 582	(3) (3) -1, 074, 455 -645, 657 -198, 356 -269, 037	45, 413, 347 54, 820, 716 44, 953, 082 57, 026, 246 64, 943, 849 70, 107, 181	37, 192, 287 45, 703, 594 31, 422, 272 41, 839, 039 49, 469, 972 54, 694, 746	81. 9 83. 4 69. 9 73. 4 76. 2 78. 0	8, 221, 060 9, 117, 122 13, 530, 810 15, 187, 207 15, 473, 877 15, 412, 435	18. 1 16. 6 30. 1 26. 6 23. 8 22. 0	

Production plus imports minus exports, plus or minus decrease or increase, respectively, of net changes in stocks.
 From Report of American Iron and Steel Institute. Figures include coke consumed in manufacture of

ferro-alloys.

3 Data not available.

Table 26.—Coke and coking coal consumed per net ton of pig iron made in the United States, 1913, 1918, and 1939-42

Year	Coke per net ton of pig iron and ferro- alloys <sup>1</sup> (pounds)	Yield of coke from coal (per- cent)	Coking coal per net ton of pig iron and ferro- alloys (pounds cal- culated)	Year	Coke per net ton of pig iron and ferro- alloys 1 (pounds)	Yield of coke from coal (per- cent)	Coking coal per net ton of pig iron and ferro- alloys (pounds cal- culated)
1913	2, 172. 6	66. 9	3, 247. 5	1940	1, 781. 2	70. 1	2, 540. 9
1918	2, 120. 7	66. 4	3, 193. 8	1941	1, 767. 8	70. 0	2, 525. 4
1939	1, 778. 0	69. 8	2, 547. 3	1942	1, 822. 8	70. 0	2, 604. 0

<sup>&</sup>lt;sup>1</sup> From Report of American Iron and Steel Institute; consumption per ton of pig iron only, excluding furnaces making ferro-alloys, was 2,172.6 pounds in 1913, 2,120.7 in 1918, 1,760.0 in 1939, 1,756.9 in 1940, 1,745.2 in 1941, and 1,791.4 in 1942.

# FURNACE, FOUNDRY, DOMESTIC, AND OTHER COKE

The terms "furnace coke" and "foundry coke," as used by the trade, refer to size and grade as well as to use. In the manufacture of byproduct coke the facilities for screening or sizing the product permit more precise definitions of grade. In terms of size, byproduct-furnace coke is run-of-oven coke, from which the breeze has been removed. Byproduct-foundry coke is blocky coke of which the maximum size is much greater than that of furnace, and from which all sizes below 2½ to 3 inches have been screened. Domestic coke generally includes a mixture of sizes approximately 3 inches and under, exclusive of breeze. It may result from the screening of foundry and furnace coke; or, where the principal demand is for domestic coke, it may be obtained by crushing the larger fragments. Other special sizes and grades are prepared for special purposes. The majority of the byproduct operators reported that their plants were equipped to screen and size coke for domestic use.

The total quantity of byproduct and beehive coke reported as "used by producers in blast furnaces" and "sold for use in blast furnaces," shown in tables 27 and 28, totaled 55,491,570 tons, whereas the quantity of coke charged into blast furnaces was 54,694,746 tons (table 25), a difference of 796,824 tons. There are two reasons for this discrepancy: (1) Tables 27 and 28 include exports to Canada and other countries, which of course are not included in the record of consumption by American furnaces; (2) tables 27 and 28 cover shipments of blast-furnace coke by producers and do not consider losses due to handling and changes in stocks at blast furnaces.

The total sales of byproduct- and beehive-foundry coke, including exports, were 2,591,576 tons compared with 2,846,459 tons in 1941. The contributing factors that led to decreased use of foundry coke were: (1) Shortages of pig iron and scrap, which diverted coke from cupolas to steel-producing plants; (2) limitation orders which limited the production of cast-iron ware to specified articles and which established quotas for each item of manufacture based upon the amount of iron so used during the year ended June 30, 1941.

The use of both byproduct and beehive coke as a domestic fuel dropped 621,265 tons (9 percent) in 1942 compared with 1941, principally because a number of merchant byproduct-coke plants which had not sold blast-furnace coke in recent years directed some of their output to the iron and steel industry.

Table 27.—Byproduct coke produced and sold or used by producer in the United States in 1942, by States [Exclusive of screenings or breeze]

										Bold				
State	Pro	duced	Used by I blast fi	oroducer in urnaces 1	Fur	nace <sup>2</sup>	Fou	ındry	Dome	stic use	other us	orial and e (includ- ter gas) <sup>3</sup>	т	otal
	Net tons	Value	Net tons	Value	Net tons	Value	Net tons	Value	Net tons	Value	Net tons	Value	Net tons	Value
Alabama. Colorado. Illinois. Indiana. Maryland Massachusetts. Michigan. Minnesots. New Jersey. New York. Ohio. Pennsylvania. Tennessee. Utah. West Virginia. Connecticut, Kentucky, Missouri, Rhode Island, and Wissouri.	5, 579, 511 676, 209 3, 690, 155 7, 337, 512 2, 103, 664 1, 176, 359 3, 139, 139, 351 1, 038, 461 5, 180, 384 9, 912, 783 16, 310, 167 234, 529 242, 631 2, 444, 368	27, 364, 122 52, 848, 043 (4) 21, 793, 813 7, 507, 413 37, 660, 727 59, 087, 481 77, 293, 489 (4)	654, 366 2, 561, 678 6, 440, 682 2, 080, 406 250, 173 1, 549, 687 305, 903 1, 901, 537 7, 749, 842 14, 049, 046 108, 582 153, 871	18, 321, 622 45, 640, 324 (4) 9, 128, 100 1, 999, 637 14, 292, 989 45, 176, 097 63, 122, 213 (4)	152, 269 (4) 20, 224 (4) 22, 202 1, 962, 138 1, 320, 460 1, 373, 584	(4) (4) (4) 12, 786, 188	4, 408 298, 203 (4) 74, 746 (4) (4) 51, 953 299, 443	(4) (4) (4) (4) (4) 2, 625, 420	101, 943 584, 558 183, 753 9, 984 788, 236 906, 753 324, 523 396, 248 1, 020, 259 315, 694 473, 115 3, 326 5, 182	3, 963, 672 1, 157, 290 (4) (4) 6, 665, 741 3, 027, 212 (4) 8, 193, 846 1, 833, 174	16, 298 109, 427 94, 747 23, 278 46, 216 238, 141 (4) 318, 199 245, 617 205, 936	802, 627 738, 596 (4) (4) 1, 817, 952 (4) (4) 1, 938, 042 1, 292, 006 1, 678, 160	20, 706 1, 144, 457 868, 424 33, 262 929, 422 1, 653, 730 707, 893 788, 602 3, 228, 014 2, 141, 533	9, 197, 553 7, 011, 839 (4) (4) 13, 151, 980 6, 062, 972 (4) 22, 918, 076 13, 749, 893 14, 513, 424
consinUndistributed	2, 273, 838	17, 935, 380 41, 058, 855		1, 193, 792 24, 216, 340	773, 330 949, 988			2, 886, 196 8, 724, 588		7, 497, 727 10, 710, 565	291, 267 106, 472		2, 163, 199	17, 289, 875 17, 178, 416
Grand total, 1942	62, 294, 909	378, 011, 967	44, 354, 642	246, 774, 609	7, 487, 582	45, 349, 578	2, 250, 564	22, 853, 858	5, 963, 474	46, 967, 968	2, 404, 323	17, 559, 705	18, 105, 943	132, 731, 109
		114, 723, 148 263, 288, 819												
														115, 101, 133

Includes 810,492 net tons valued at \$5,138,252 used to make producer gas; 1,527,191 tons, \$8,440,530, used to make water gas; and 414,009 tons, \$2,504,247, used for other purposes than in blast furnaces.

Includes 3,515,351 net tons valued at \$19,373,565 sold to financially affiliated corporations for blast-furnace use; 729,619 tons, \$4,638,839, sold for other purposes; and 3,242,612 tons, \$1,037,174, reported as merchant sales.

Includes 657,761 net tons valued at \$5,131,790 sold for manufacture of water gas.

Table 28.—Beehive coke produced and sold or used by producers in the United States in 1942, by States

State	Prod	luced	Used by problem blast fu		Sold Furnace 2		
	Net tons	Value	Net tons	Value	Net tons	Value	
Alabama. Colorado and Utah Kentucky and Tennessee. Pennsylvania. Virginia. West Virginia. Undistributed.	95, 428 109, 849 73, 679 7, 309, 337 350, 521 335, 221	\$591, 646 (3) (3) 41, 263, 580 2, 281, 289 2, 066, 217 1, 399, 045	(3) (3) (3) 505, 251 (3) 198, 884	(3) (3) (3) \$2, 635, 989 (3) 1, 404, 552	35, 821 4, 731 5, 888 6, 055, 834 161, 563 165, 442	\$287, 552 (3) (3) 34, 018, 152 1, 047, 837 860, 146 73, 612	
Total: 1942 1941	8, 274, 035 6, 704, 156	47, 601, 777 36, 490, 006	704, 135 1, 015, 752	4, 040, 541 4, 977, 767	6, 429, 279 4, 805, 099	36, 287, 299 26, 280, 276	

				Sold-	-Continue	đ			
State	Net tons		Foundry Domestic use			rial and se (includ- ster gas) 4	Total		
		Value	Net tons	Value	Net tons	Value	Net tons	Value	
Alabama. Colorado and Utah. Kentucky and Tennessee. Pennsylvania. Virginia West Virginia. Undistributed	663 3, 618 234, 476 56, 342 45, 913	(3) \$1, 629, 050 395, 716 346, 196 32, 258	306 89, 385 3, 000 5, 529	\$1,563 500,560 15,233 27,174	184 16, 902 9, 622 433, 098 130, 322 120, 323	\$1, 133 (3) 2, 531, 364 828, 519 846, 863 172, 081	36, 005 22, 602 19, 128 6, 812, 793 351, 227 337, 207	\$288, 685 (3) (3) 38, 679, 126 2, 287, 305 2, 080, 379 279, 514	
Total; 1942 1941	341, 012 352, 066	2, 403, 220 2, 283, 630	98, 220 85, 990	544, 530 424, 736	710, 451 433, 472	4, 379, 960 2, 445, 619	7, 578, 962 5, 676, 627	43, 615, 009 31, 434, 261	

<sup>&</sup>lt;sup>1</sup> Includes 2,305 net tons valued at \$12,420 used for other purposes than in blast furnaces.

<sup>2</sup> Includes 1,542,503 net tons valued at \$7,570,393 sold to financially affiliated corporations for blast furnace use; 452 tons, \$2,179, sold for other purposes; and 4,886,324 tons, \$28,714,727, reported as merchant sales.

<sup>3</sup> Included under "Undistributed."

Includes 115,265 net tons valued at \$691,508 sold for manufacture of water gas.

### STOCKS OF COKE AND COKING COAL

Table 29 gives details of the quantity of coke and coke breeze on hand at all beehive and byproduct plants as of January 1, 1943. cording to reports from byproduct-coke plants, stocks of furnace and foundry coke totaled 792,072 tons, domestic coke 661,401 tons, and coke breeze 655,175 tons. Stocks of metallurgical coke increased 10 percent during the year, but stocks of domestic coke decreased 33 percent. The decrease in stocks of domestic coke was general at merchant plants in 1942, as many producers were forced to draw from stocks because the current production was directed to the heavy industries.

In the operations of beehive ovens, the output is governed by the sales, and ordinarily stocks are negligible. Producers' stocks of beehive coke totaled 35,576 tons on January 1, 1943. Of this amount, 24,617 tons (69 percent) was blast-furnace coke, 2,203 tons foundry coke, and 8,756 tons domestic coke. Table 30 summarizes total stocks, by grades, at all byproduct and beehive plants as of January 1, 1929, and 1939-43. The stocks of coke on hand at producers' plants by months for 1941 and 1942 are shown in table 31. These data show that stocks of coke carried by furnace plants remained relatively constant, but stocks of coke at merchant plants showed seasonal fluctuations.

Generally stocks of bituminous coal held by byproduct operators closely follow the trend of monthly production. In 1942, however, operators were advised by the Office of Solid Fuels Coordinator for War to build and maintain their stock piles of coking coal to full storage capacity, so that maximum production could be maintained if their normal supply was curtailed. On January 1, 1942, stocks of coking coal at byproduct plants totaled 8,901,462 tons, a 37.7-day supply at the December rate, and they steadily increased until, by December 31, 1942, stocks on hand amounted to 10,721,414 tons, enough for 43.8 days' requirements at the rate of consumption prevailing in December 1942.

Table 29.—Stocks of furnace, foundry, and domestic coke and of breeze in the United States on January 1, 1943, by States, in net tons

			Breeze		
State	Furnace	Foundry	Domestic and other	Total	Breeze
Byproduct plants:					
Alabama	186, 691	1 040		000 040	
Colorado	100, 091	1, 342	20, 313	208, 346	61,840
Illinois.	5,866			5,866	711
T. diam.	79, 669	785	12, 624	93, 078	73, 119
Indiana	24, 795	2, 233	8, 207	35, 235	26, 815
Maryland	40, 036			40,036	81, 464
Massachusetts	380	138	143, 759	144, 277	5,521
Michigan	3.708	3, 839	30, 571	38, 118	35, 791
Minnesota	2,306		37, 148	39, 454	21, 633
New Jersey		178	33, 582	33, 760	1, 982
New Jersey New York	37, 268	F	175, 132	212, 400	79, 829
Ohio.	131, 039	9, 455	59, 953	200, 447	148, 144
Pennsylvania	223, 974	0, 200	20, 967	244, 941	79, 761
Tennessee.	7, 933		20, 801	7, 933	1, 525
Utah	12, 254		4,887		
West Virginia.	9, 687	540		17, 141	686
Connecticut, Kentucky, Missouri,	3,001	040	13, 732	23, 959	11,550
Rhode Island, and Wisconsin	4, 529	3, 427	100, 526	108, 482	24, 804
	770, 135	21, 937	661, 401	1, 453, 473	655, 175
At merchant plants	47, 659	21,068	559, 371	628, 098	166, 443
At furnace plants	722, 476	869	102, 030	825, 375	
are resistance president and a second	122, 110	309	102, 000	820, 810	488, 732
Beehive plants:					
Alabama	E 771 E				
Colorado and Utah	5, 715			5, 715	
Colorado and Otan	655		226	881	102
Kentucky and Tennessee	2, 178	1,010		3, 188	
Pennsylvania.	13, 337	660	6, 467	20, 464	4, 834
Virginia		138	277	1,988	20
West Virginia	1, 159	395	1,786	3, 340	
원인 기계 기계 기계 기계 기계 기계 기계 기계 기계 기계 기계 기계 기계	24, 617	2, 203	8, 756	35, 576	4, 956

Table 30.—Summary of total stocks of coke on hand at all byproduct and beehive plants in the United States on January 1, 1929 and 1939-43, in net tons

[Exclusive of screenings or breeze]

	1929	1939	1940	1941	1942	1943
Byproduct plants: Furnace	750, 318	931, 644	597, 550	525, 798	697, 898	770, 135
Foundry Domestic and other	24, 426 1, 018, 205	88, 334 2, 611, 645	49, 771 1, 922, 369	14, 123 1, 373, 213	20, 448 991, 045	21, 937 661, 401
	1, 792, 949	3, 631, 623	2, 569, 690	1, 913, 134	1, 709, 391	1, 453, 473
Beehive plants: Furnace Foundry Domestic and other	38, 446 8, 020 8, 511	7. 228 8, 336 29, 367	16, 402 8, 312 7, 695	16, 022 3, 973 23, 313	20, 311 4, 987 23, 397	24, 617 2, 203 8, 756
	54, 977	44, 931	32, 409	43, 308	48, 695	35, 576
Total: Furnace Foundry Domestic and other	788, 764 32, 446 1, 026, 716	938, 872 96, 670 2, 641, 012	613, 952 58, 083 1, 930, 064	541, 820 18, 096 1, 396, 526	718, 209 25, 435 1, 014, 442	794, 752 24, 140 670, 157
	1, 847, 926	3, 676, 554	2, 602, 099	1, 956, 442	1, 758, 086	1, 489, 049

Table 31.—Total stocks of coke at all furnace and nonfurnace byproduct plants in the United States on first of each month, 1941-42, in net tons

[Includes furnace, foundry, and domestic, but not breeze]

	Furnace	plants	Other p	lants	Total		
Month	1941	1942	1941	1942	1941	1942	
January February March April May June July August September October November December	742, 306 731, 845 773, 666 845, 329 694, 433 741, 425 849, 320 873, 591 949, 868 880, 824 870, 731 817, 004	825, 263 817, 492 869, 318 920, 491 962, 675 974, 995 969, 315 998, 690 1, 025, 617 1, 021, 045 954, 999 917, 421	1, 170, 828 864, 873 617, 759 491, 967 706, 203 663, 714 578, 343 576, 752 661, 906 698, 764 744, 925 850, 750	884, 128 692, 293 516, 283 509, 134 485, 461 457, 309 435, 318 470, 371 538, 880 593, 106 650, 532 728, 355	1, 913, 134 1, 596, 718 1, 391, 425 1, 337, 296 1, 400, 636 1, 405, 139 1, 427, 663 1, 450, 343 1, 579, 588 1, 611, 774 1, 579, 588 1, 615, 656 1, 667, 754	1, 709, 391 1, 509, 781 1, 385, 601 1, 429, 621 1, 448, 136 1, 432, 30. 1, 404, 633 1, 469, 061 1, 564, 497 1, 614, 151 1, 605, 531	

Table 32.—Stocks of bituminous coal at byproduct-coke plants in the United States at end of each month, 1939-42, in net tons

Month	1939	1940	1941	1942
January February March April May June July August September October November December	7, 373, 871 7, 372, 654 7, 221, 632 4, 434, 124 2, 598, 470 3, 548, 326 4, 534, 922 5, 631, 984 6, 220, 015 7, 250, 436 8, 114, 807 7, 992, 848	6, 613, 253 5, 978, 167 5, 273, 567 5, 217, 870 6, 506, 396 7, 448, 266 7, 831, 640 8, 860, 832 9, 711, 983 10, 091, 259 10, 184, 443	9, 886, 936 9, 889, 674 9, 853, 544 4, 969, 862 4, 725, 310 5, 912, 874 6, 215, 277 7, 205, 844 7, 291, 698 8, 371, 329 8, 327, 472 8, 901, 462	8, 178, 962 7, 888, 481 7, 881, 459 8, 408, 907 9, 179, 025 9, 866, 281 9, 922, 306 10, 238, 114 10, 565, 801 10, 997, 933 11, 150, 840 10, 721, 414

# VALUE AND PRICE

The term "value" as used in this report means the value of coke at the ovens. For that part of the output sold, the value is the amount received for the coke, f. o. b. ovens. A considerable amount (over

The second secon

63 percent) of the coke produced in the United States is made in ovens operated by large corporations, which not only mine the coal they use for the manufacture of coke but also operate blast furnaces that consume almost all of the output of their ovens. Under such conditions, fixing a value for coal charged and for coke produced is purely arbitrary. With some corporations, the cost of coke to the furnace department equals the cost of production; with others a margin is added, or the cost is considered to be the market price.

The average receipts per ton of coke sold in 1942 increased over those of the previous year because of higher coal costs and increased manufacturing costs. Byproduct- and beehive-coke prices in 1942 were governed by maximum price regulations and are discussed in another section of this report. According to sales data furnished by the operators, average receipts per ton of byproduct coke sold in 1942 increased over the 1941 figures as follows: Furnace coke from \$5.23 to \$6.06; foundry from \$9.76 to \$10.15; domestic from \$6.96 to \$7.88; and other industrial from \$6.68 to \$7.30. Beehive coke showed the following price increases per ton: Furnace coke increased from \$5.47 to \$5.64; foundry from \$6.49 to \$7.05; domestic from \$4.94 to \$5.54; and other industrial from \$5.64 to \$6.17.

Table 33.—Average receipts per net ton for coke sold in the United States in 1942, by States

		Bypr	oduct			Вее	hive	
State	Fur- nace 1	Found- ry	Domes- tic	Other industrial, including water gas		Found-	Domes- tic	Other indus- trial, in- cluding water gas
Alabama Colorado Illinois Indiana	\$5. 16 7. 95 (2)	\$8.35 (2) 10.80 (2)	\$4.80 6.78 6.30	\$6.42 (2) 7.33 7.80	\$8.03	(2)		\$6. 16 (2)
Maryland Massachusetts Michigan Minnesota New Jersey New York	(2) (2) (2)	(2) (2) (2) (2) (2)	(2) (2) 7.35 9.33 (2) 8.03	(2) (2) 7.63 (2) (2) 7.89				
New York. Ohio	6.06	8.77 10.76 (²)	5. 81 7. 25 (2)	7. 89 6. 27 7. 14 (2) (2)	5, 62 (2) (2) (2) 6, 49	\$6.95 (2) (2) 7.02	\$5. 60 5. 11 5. 08	5, 84 (2) (2) (2) 6, 36
West Virginia Connecticut, Kentucky, Missouri, Rhode Island, and Wisconsin Undistributed	(2) 5. 96 7. 09	(2) 11.61 10.61	(2) 8. 82 8. 90	7. 90 7. 39	5, 20 6, 93	7. 54 7. 54 5. 40 7. 81	4. 91	6. 41 6. 49
United States average	6.06	10.15	7.88	7.30	5. 64	7.05	5. 54	6. 17
At merchant plants At furnace plants	6. 64 5. 53	10. 34 9. 07	8. 09 6. 65	7. 55 6. 49	,			

<sup>&</sup>lt;sup>1</sup> Includes coke sold to affiliated corporations for all other purposes and merchant sales.
<sup>2</sup> Included under "Undistributed,"

Table 34.—Average monthly prices per net ton at ovens of spot or prompt Connellsville furnace and foundry coke, 1929 and 1939–42  $^1$ 

		Fu	rnace col	ke		Foundry coke				
Month	1929	1939	1940	1941	1942	1929	1939	1940	1941	1942
January	\$2,75	<b>\$3.</b> 75	\$4, 20	\$5. 50	\$6.13	\$3.75	\$4.75	\$5, 50	\$5. 75	\$6,88
February	2.90	3.75	4.00	5. 50	6.00	3.75	4.75	5. 31	5.75	6.88
March	2.98	3, 75	4.00	5. 52	6.00	3, 75	4.75	5. 25	5.85	6.88
April /	2.78	3, 75	4.00	5. 63	6.00	3. 75	4.75	5. 25	5, 62	6, 88
May	2.75	3, 75	4.00	6.00	6.00	3, 75	4, 75	5. 25	6, 72	6, 88
June	2.75	3, 75	4.00	6, 13	6.00	3, 75	4. 75	5. 25	6.88	6. 88
July	2.75	3, 75	4. 20	6. 13	6.00	•3.75	4. 75	5. 25	6.88	6.88
August	2.73	3, 75	4.63	6. 13	6.00	3, 75	4, 75	5. 25	6.88	6.88
September	2.65	4. 25	4. 75	6. 13	6,00	3, 75	5. 12	5. 25	6.88	6.88
October	2.65	4.90	4. 75	6.13	6.00	3, 75	5. 65	5. 25	6.88	6. 88
November	2.65	5.00	5. 10	6. 13	6.00	3, 75	5. 75	5.63	6.88	6.88
	2.64	5.00	5.38	6. 13	6.00	3, 75	5. 75	5. 75	6.88	6.88
December	4.04	0.00	0.00	0. 10	0.00	5. 10	5, 10	5, 10		6. 88
Average	2.75	4.09	4.42	5. 92	6. 01	3.75	5. 02	5.35	6.49	6.88

<sup>&</sup>lt;sup>1</sup> Iron Age.

## SHIPMENTS BY RAIL, WATER, AND TRUCK

Table 35.—Beehive coke loaded for shipment on originating railroads, waterwary, and trucks in the United States in 1942, by routes, as reported by coke producers

선물이 하늘 사실 명하는데 이번 경기		Net	tons	Percent
Route	State	By States	Total	of total
Railroads:  Baltimore & Ohio Chesapeake & Ohio Denver & Rio Grande Western Huntingdon & Broad Top Mountain Interstate Ligonier Valley Louisville & Nashville Monongahela Nashville, Chettanooga & St. Louis New York Central Norfolk & Western Pennsylvania Pittsburgh & Lake Erie Western Maryland Total railroad shipments Waterways: Monongahela and Ohio Rivers Trucks. Grand total	West VirginiaPennsylvania	44, 921 92, 987 23, 103 16, 772 309, 339 74, 965 36, 734 496 1, 906, 496 1, 905, 579 183, 335 41, 734 3, 250, 588 86, 731 4, 729	} 1, 670, 203 44, 921 116, 090 16, 772 309, 339 74, 965 37, 230 1, 906, 497 18, 579 183, 335 41, 734 3, 250, 588 86, 731 4, 729 7, 761, 713 140, 53 37, 596 7, 939, 872	24. 0 . 2 2. 3 . 5 40. 9 1. 1 . 1 97. 7 1. 8

<sup>&</sup>lt;sup>1</sup> Coke delivered by trucks to consumers in all States that produced beehive coke.

#### DISTRIBUTION OF BYPRODUCT AND BEEHIVE COKE IN 1942

The unusually heavy demand for coke in 1942 by various war industries created widespread interest in coke production and distribution data. It is believed therefore that the statistics presented in the following tables showing geographic distribution of coke, by uses, will have interest and value to producers and consumers, and to war agencies responsible for the maintenance of adequate supplies of coke at war plants. The statistical data produced by the survey show (1) coke consumed in each State in 1942 by principal uses and (2) comparable tonnages of coke consumed in each State and region, by uses, from 1940 to 1942. The tonnages shipped to each destination represent

THE PROPERTY OF THE PROPERTY O

approximately the coke consumed therein, and for practical purposes the terms "distribution" and "consumption" are used here inter-

changeably.

The total consumption of coke in 1942, excluding imports, increased 8 percent from that in 1941 and reached 70,110,497 tons. This rise in consumption was due to the increased activities in the various industries producing essential war material. The tonnage of coke used in blast furnaces increased 5,058,458 tons, but the outstanding development in the distribution of coke in 1942 was the gain in the quantity used for the manufacture of water gas and for miscellaneous industrial purposes, which increased 23 and 27 percent. With the diversion of coke from the domestic trade to the iron and steel industry, the downward trend of domestic consumption that began in 1940 continued through 1942, when coke for domestic use dropped 734,831 tons. The quantity of coke used in foundries dropped 211,559 tons in 1942 compared with 1941, for reasons explained on page 978.

Furnace coke was used in 25 States in 1942. The great centers of consumption were naturally the iron- and steel-producing districts in Pennsylvania, Ohio, Indiana, Illinois, and Alabama, which took 81 percent of the total furnace coke used. Foundry coke was used in all States but 1; coke for the manufacture of water gas in 33 States; and unclassified industrial coke in all but 1 State. The largest tonnages of that classed as "other industrial" were consumed in Pennsylvania, New York, and Michigan. Coke used for domestic heating was distributed to all but 9 States. New York consumed almost

one-fifth of the coke used for domestic purposes.

The distribution of coke by uses, by regions, increased in seven of the nine regions as classified (table 37). Outstanding was the increased consumption of 1,909,297 tons (26 percent) in the Southeast region because of an expanded iron and steel industry, chiefly in Alabama and West Virginia. The Middle Atlantic region increased its coke consumption by 7 percent, mainly because of the gain in tonnage of coke used for steelmaking in Pennsylvania. The only regions that showed decreased consumption in 1942 compared with 1941 were the Missouri Valley and the Lake Dock regions. Here decreases resulted from diminished consumption by foundries and for domestic heating.

Table 36.—Summary of byproduct and beehive coke and breeze consumed in each State in 1942, in net tons

[Based upon reports from all United States producers showing destination of coke used by producer or sold in 1942. Does not include imported coke, which totaled 108,782 net tons in 1942]

				Coke				
Consuming State	Furnace use	Foundry use	Making pro- ducer gas	Making water gas	Other indus- trial use	Domes- tic use	Total	Coke breeze
Alabama		167, 189		922			5, 233, 646	290, 69
Arizona		5, 925			455		6, 380	
Arkansas		759		(1) (1)	(1)	(1)	1,659	1,94
Arkansas California	24, 326	62, 677		(1)	(1)	(1)	125, 646	25
Colorado Connecticut Delaware District of Columbia	(1)	(1)			31, 556		695, 653	(1)
Jonnecticut	-	51, 646	(1)	(1)	(1)	(1)	424, 744	
Jelaware	_ 38	(1)			(1)	(1)	(1)	2,47
District of Columbia	-			65, 023	(1)	1, 517	(1)	
Florida Georgia		2,410		36, 201	5, 113			(1)
deorgia	1,005	19, 289		8, 591	8,040		47, 436	
daho		633			3, 494		4, 127	
llinois	4, 712, 040	232, 981	27, 885	50, 133	127, 435	472, 060	5, 622, 534	327, 4
Indiana Iowa	. 5, 562, 396	113, 748		34, 069				432, 89
owa		42, 138		6, 330		9, 496	93, 730	20, 56
Kansas		10, 127			(1)		(1)	1,64
Kansas Kentucky	400, 108	21, 153		51, 901	18, 616	43, 359		8, 97
Louisiana		3,811			25, 528	5, 496		
Aaine		5, 652		3, 096		46, 681	55, 429	127, 22
Maryland	2, 220, 653	25, 746		13, 871	49, 741	13, 067	2, 323, 078	127, 22
Massachusetts	. 144, 885	(1)	96, 236	79, 111	(1)	792, 500	1, 202, 069	108.90
Michigan	1, 397, 755	278, 501	26, 993	5, 367	317, 981	795, 712	2,822,309	186, 03
Massachusetts Michigan Minnesota	(1)	27, 981	(1)	(1)	44, 655	304, 232	682,717	54, 15
vississippi		(1)			2, 346	(1)	4,042	
Missouri		51, 410		888	65, 954	147, 821	266, 073	74
Missouri Montana Jehraska	(1)	3, 120			(1)		42, 943	
		(1)		13, 932	6, 287	894	23, 933	
Vevada		30			8, 216		8, 246	8
New Hampshire		5, 169		1, 330	138	50,006	56, 643	
New Jersey New Mexico New York	980	130, 799	104, 814	282, 225	112, 075	408, 102	1,038,995	103, 25
New Mexico		1,664			264		1,928	
New York	3, 827, 457	189, 590	306, 518	731, 897	329, 935	1,063,593	6, 448, 990	402, 99
North Carolina		17, 298		5, 222	3, 539	1,861	27, 920	(1)
North Dakota		(1)		(1)	(1)	(1)	2,017	
North Carolina North Dakota Dhio	11, 685, 420	339, 946	2, 166	35, 787	162, 340		12, 529, 262	673, 13
JKIANOMA	1	4, 064 7, 784			345	771	5, 180	29,88
Oregon Pennsylvania		7, 784			5, 278	36	13,098	10
ennsylvania	[17, 855, 365]	311, 934	82, 364	112, 283	391, 444	428, 456	19, 181, 846	1, 347, 84
Knode Island		19, 112	(1)	(1) (1)	(1)	(1)	191, 618	(1)
inith Carolina	1 951	5, 265		(1)	(1)	(1)	31, 765	5, 22
South Dakota		212			431	1,657	2, 300	
ennessee		72, 203		2,653	135, 083	4,744	439, 306	81,79
Cexas	(1)	24, 210		(1)	(1)	36	59, 624	16,08
Itah		15, 288			61, 286	3, 484	235, 588	22, 11
/ermont		8, 729		1,873	3, 045	16,688	30, 335	
/irginia	(1)	48, 043	40	358, 880	82, 354	(1)	573, 512	(1)
Vashington		8, 260	169		4, 186		12,615	
Vest Virginia	1, 281, 959	31, 739		691, 360	192, 986	1, 774	2, 199, 818	143, 73
v isconsin	[ (1) [	120, 400	(1)	35, 868	(1)	345, 540	575, 867	108, 46
Vyoming					2, 174		2, 174	2
Jndistributed	1,068,572	87, 333	175, 298	88, 022	148, 548	361, 250	94, 835	121,04
TT 11 1 01 1								
United States, total	55, 390, 133	2, 575, 968	822, 483	2, 716, 835	2, 679, 062	5, 926, 016	70, 110, 497	
Exported	101, 437	98, 443	5, 528	300	232, 665	194, 812	633, 185	65, 16
Constituted	FF. 401 FT	0.074.455	000.01					
Grand total	100. 491. 5701	z. 674. 4111	X2X. 0111	2 717 135	7. UII 797	6 19N <b>2</b> 92	70, 743, 682	A 700 88

<sup>&</sup>lt;sup>1</sup> Included under "Undistributed."

Table 37.—Comparative tonnages of byproduct and beehive coke consumed in each State and region, 1940-42, in net tons
[Exclusive of imported coke and of screenings or breeze]

•		Furnace use		F	oundry use	э	Other indu	strial and do	mestic use		Total coke	
Consuming region and State	1940	1941	1942	1940	1941	1942	1940	1941	1942	1940	1941	1942
New England: Maine New Hampshire Vermont Massachusetts Connecticut Rhode Island	88, 830	(2)	144, 885	(1) 1,443 5,433 48,872 34,847 (1)	(1) (1) 8, 141 (2) 48, 562 15, 613	5, 652 5, 169 8, 729 (1) 51, 646 19, 112	1 54, 610 57, 325 35, 878 1, 095, 954 331, 674 1 189, 393	1 61, 588 1 60, 066 26, 719 2 1, 200, 719 350, 768 178, 403	49, 777 51, 474 21, 606 11, 057, 184 373, 098 172, 506	54, 610 58, 768 41, 311 1, 233, 656 366, 521 189, 393	61, 588 60, 066 34, 860 1, 200, 719 399, 330 194, 016	55, 429 56, 643 30, 335 1, 202, 069 424, 744 191, 618
•	88, 830	(2)	144, 885	90, 595	72, 316	90,308	1, 764, 834	1, 878, 263	1, 725, 645	1, 944, 259	1, 950, 579	1, 960, 838
Middle Atlantic: New York New Jersey Pennsylvania Delaware Maryland District of Columbia	14, 319, 836 764	3, 395, 181 105 16, 663, 593 284 1, 920, 995	3, 827, 457 980 17, 855, 365 38 2, 220, 653	141, 372 86, 161 219, 232 2, 758 23, 891 395	201, 752 122, 896 331, 451 4, 227 36, 550	189, 590 130, 799 311, 934 (1) 25, 746	2, 947, 521 921, 763 850, 635 3, 524 85, 487 66, 935	2, 595, 437 893, 128 872, 523 8, 987 85, 284 1 62, 335	2, 431, 943 907, 216 1, 014, 547 (1) (3) 76, 679 8 80, 412	5, 704, 001 1, 008, 575 15, 389, 703 7, 046 1, 959, 295 67, 330	6, 192, 370 1, 016, 129 17, 867, 567 13, 498 2, 042, 829 62, 335	6, 448, 990 1, 038, 995 19, 181, 846 (3) 2, 323, 078 8 80, 450
OhioMichigan	18, 786, 276 8, 619, 762 1, 076, 370	21, 980, 158 11, 005, 454 1, 058, 522	23, 904, 493 11, 685, 420 1, 397, 755	473, 809 304, 373 333, 791	696, 876 307, 127 415, 126	658, 069 339, 946 278, 501	4, 875, 865 652, 815 1, 389, 182	4, 517, 694 628, 719 1, 034, 768	4, 510, 797 503, 896 1, 146, 053	24, 135, 950 9, 576, 950 2, 799, 343	27, 194, 728 11, 941, 300 2, 508, 416	29, 073, 359 12, 529, 262 2, 822, 309
Illinois-Indiana: Illinois Indiana	3, 332, 028 4, 305, 518	4, 369, 826 5, 231, 850	4, 712, 040 5, 562, 396	172, 455 106, 063	241, 538 145, 936	232, 981 113, 748	857, 653 518, 413	790, 831 434, 610	677, 513 375, 104	4, 362, 136 4, 929, 994	5, 402, 195 5, 812, 396	5, 622, 534 6, 051, 248
	7, 637, 546	9, 601, 676	10, 274, 436	278, 518	387, 474	346, 729	1, 376, 066	1, 225, 441	1, 052, 617	9, 292, 130	11, 214, 591	11, 673, 782
Missouri Valley: Missouri	.	121 108	(5)	34, 426 33, 721 2, 320 7, 510	51, 836 52, 074 5, 987 10, 690	51, 410 42, 138 5 2, 820 10, 127	313, 661 42, 101 4 20, 996 2, 837	209, 270 44, 078 23, 200 3, 467	214, 663 51, 592 21, 113 (6)	367, 231 75, 822 23, 316 10, 347	261, 227 96, 152 29, 295 14, 157	266, 073 93, 730 23, 933 ( <sup>6</sup> )
	19, 144	229	(5)	77, 977	120, 587	106, 495	379, 595	280, 015	287, 368	476, 716	400, 831	383, 736
Lake Dock region: Wisconsin Minnesota North Dakota South Dakota	225, 569	30 282, 693	(4) (4)	99, 327 15, 684	139, 350 24, 764 ( <sup>7</sup> ) (¹) ( <sup>7</sup> )	120, 400 27, 981 (¹) 212	553, 703 373, 685 1, 758 1 2, 449	333, 202 1, 596	4 455, 467 4 654, 736 1 2, 017 2, 088	653, 030 614, 938 1, 758 2, 449	630, 928 640, 659 (7) 7 4, 523	575, 867 682, 717 2, 017 2, 300
	225, 569	282, 723	(4)	115, 011	164, 114	148, 593	931, 595	829, 273	1, 114, 308	1, 272, 175	1, 276, 110	1, 262, 90
								-		-	=====	

See footnotes at the end of table.

Table 37.—Comparative tonnages of byproduct and beehive coke consumed in each State and region, 1940-42, in net tons—Continued

Consuming region and State		Furnace use		1	Foundry us	е	Other indu	istrial and do	mestic use		Total coke	
Consuming region and State	1940	1941	1942	1940	1941	1942	1940	1941	1942	1940	1941	1942
utheast: Virginia West Virginia I North Carolina South Carolina Georgia Florida Kentucky Tennessee Alabama Mississippi	4 276 223	74, 491 874, 483 192 64 1, 220 281, 364 140, 162 4, 140, 855	1, 281, 959 25 1, 005 400, 108 224, 623 4, 826, 996	31, 258 12, 657 13, 410 3, 613 13, 765 1, 017 20, 341 59, 724 123, 394	46, 514 25, 678 15, 406 4, 397 19, 147 1, 641 21, 897 76, 177 164, 668 1, 060	48, 043 31, 739 17, 298 5, 265 19, 289 2, 410 21, 153 72, 203 167, 189	383, 798 479, 082 10, 522 5, 896 26, 435 35, 251 (4) 63, 113 142, 084 1 2, 206	443, 298 546, 166 10, 225 6, 321 26, 644 35, 166 59, 549 76, 124 135, 433 2, 590	4 525, 469 886, 120 10, 622 26, 475 27, 142 45, 237 113, 876 142, 480 239, 461 1 4, 042	467, 771 1, 279, 433 23, 932 9, 509 40, 200 36, 268 296, 564 177, 149 4, 364, 912 2, 206	564, 303 1, 446, 327 25, 823 10, 782 47, 011 36, 807 362, 810 292, 463 4, 40, 956 3, 650	573, 51 2, 199, 81 27, 92 31, 76 47, 43 47, 64 535, 13 439, 30 5, 233, 64 4, 04
L.	5, 270, 378	5, 512, 831	6, 734, 716	279, 179	376, 585	384, 589	1, 148, 387	1, 341, 516	2, 020, 924	6, 697, 944	7, 230, 932	9, 140, 22
outhwest, Mountain, and Pacific: Louisiana Arkansas. Oklahoma Texas. New Mexico Arizona Colorado Utah Nevada Wyoming Montana Idaho Washington Oregon California	16, 286 521, 698 163, 790	18, 824 - 573, 925 - 224, 725 - 23, 988	(4) <sup>8</sup> 664, 097 155, 530 <sup>4</sup> 39, 823	2, 883 1, 444 2, 205 15, 991 (1) 4, 063 11, 604 10, 337 2, 28 2, 060 (1) 3, 089 2, 821 47, 720	3, 785 (*)  * 4, 734 24, 471 1, 259 6, 500 21, 969 18, 074 (56 (1) 2, 515 2, 873 8, 111 4, 871 72, 657	3, 811 759 4, 064 24, 210 1, 664 5, 925 (5) 15, 288 30 3, 120 633 8, 260 7, 784 62, 677	29, 030 605 191 15, 348 1, 237 2, 592 57, 347 2, 472 3, 239 1, 630 1, 788 10, 960	29, 702 (9) 61, 008 18, 016 360 387 20, 246 (4) 6, 857 17, 949 5, 200 2, 640 3, 469 5, 056 24, 368	31, 024 1, 116 4 35, 414 455 31, 556 64, 770 8, 216 2, 174 (4) 3, 494 4, 355 5, 314 38, 643	31, 913 2, 049 2, 396 47, 625 1, 237 4, 348 545, 894 231, 474 24, 793 3, 900 4, 719 4, 609 67, 680	33, 487 (9) 8 5, 742 61, 311 1, 619 6, 887 616, 140 242, 799 31, 703 5, 513 11, 580 9, 927 117, 400	34, 83; 1, 65; 5, 18; 59, 62; 1, 92; 6, 38; 695, 65; 23, 5, 58; 8, 24; 2, 17; 42, 94; 42, 12; 112, 61; 13, 609; 125, 646

Foundry and other industrial combined.
 Furnace, foundry, and other industrial combined.
 Delaware and District of Columbia combined.
 Furnace and other industrial combined.

Furnace and foundry combined.
Bureau of Mines not at liberty to publish.
North and South Dakota combined.
Arkansas and Oklahoma combined.

#### EXPORTS AND IMPORTS

Exports of coke from the United States totaled 839,582 net tons valued at \$6,349,801 in 1942—an increase of 130,611 tons over 1941. The principal export movement of coke in 1941 and 1942 was to Canada, which received 89 percent of all exported coke in 1941 and 96 percent in 1942. Aside from Canada, the export market for American coke is small, although South America received 54,585 tons in 1941 and 18,466 tons in 1942. The increase in exports of coke to South America in 1941 may be traced to World War II. Normally South America received most of its coke for metallurgical purposes from Germany and Great Britain. With those countries at war in 1941, South America turned to the United States for its supply. In 1942 the export movement of coke to South America decreased sharply, both because of increased requirements within the United States and because of shipping difficulties.

Imports of coke supply a very minor part of United States requirements and are a factor in the home market in restricted localities only. In 1941 267,886 tons of coke were imported. Of this amount, Great Britain supplied 178,209 tons (67 percent) and Canada, 89,677 tons (33 percent). In 1942, 108,782 tons were imported, and of this amount 97,386 tons came from Canada and 3,819 tons from Great Britain. In addition, Mexico sent the United States more coke than was exported to it, all of which came through the El Paso and Laredo customs districts. Imports from Canada have remained approximately the same during the past 3 years, although the 97,386 tons

received in 1942 exceeded the 1941 figure by 7,709 tons.

Table 38.—Coke exported from the United States, 1940-42, by customs districts

	19	40	19	41	1942		
Customs district	Net tons	Value	Net tons	Value	Net tons	Value	
Buffalo	304, 390	\$1,676,244	225, 119	\$1, 461, 672	280, 085	\$1, 995, 909	
Chicago	11, 128	41, 752	24, 714	194, 536	6, 395	18, 558	
Dekote	5 864	47,007	7, 007	63, 437	18, 472	158, 673	
Duluth-Superior	11, 427	71, 225	3, 414	34, 588	9, 296	86, 835	
Florida	5,851	53, 166	3, 504	40, 201	4, 487	56, 119	
Laredo	18, 696	153, 449	3, 888	33, 920	1, 335	13, 962	
Maryland	1 9,006	76, 866	16, 085	167, 751	2,926	27, 134	
Michigan	371, 125	2, 220, 943	315, 363	2, 374, 350	417, 608	3, 300, 448	
Mobile	9, 825	186, 565	- 5, 329	82,021	7, 135	66, 957	
New Orleans	8, 112	78, 341	4, 805	52, 390	3, 937	59, 880	
New York	11, 868	132, 735	20, 675	326, 492	5, 704	111, 585	
Ohio	17, 982	116, 369	42, 951	160, 182	70, 819	331, 769	
Philadelphia		80, 448	13, 020	162, 590			
St. Lawrence		4, 279	4, 368	45, 252	3, 506	30, 977	
an Diego		7, 121	1, 146	6,748	503	7, 176	
an Francisco		134	10	290	6	167	
Virginia.		68, 376	10, 070	122, 714	6, 767	75, 164	
Other districts	1, 244	9, 972	7, 503	60, 171	601	8, 49	
	804, 095	5, 024, 992	708, 971	5, 389, 305	839, 582	6, 349, 80	

<sup>&</sup>lt;sup>6</sup> Figures on exports and imports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Table 39.—Coke exported from the United States, 1940-42, by countries

Country	19	940	19	941	19	42
	Net tons	Value	Net tons	Value	Net tons	Value
North America:						
Canada	722, 740	04 100 000	400 000		212 212	
Mexico		\$4, 182, 630	630, 271	\$4, 390, 888	806, 517	\$5, 925, 858
Panama	19,922	165, 196	5, 167	42, 344	2,032	23, 49
West Indies:	158	3, 370	267	6,604	111	2, 40
Cuba	19, 787	168, 234	0.450	00.000		
Trinidad and Tobago	10, 101	100, 204	9, 458	96, 992	11,760	123, 510
Other North America	453		102	1, 183		
South America:	400	5, 944	882	16, 833	475	9, 29
Argentina	1,557	13, 575	23, 164	325, 888	- 040	<b>=</b> 0.00
Bolivia	264	4, 542	399		5,048	79,087
Brazil.	5, 512	51, 660		7, 401	200	3, 349
Chile	1,493	17, 409	16, 122	185, 483	4,742	81, 314
Peru			13, 811	174, 565	7, 417	75, 719
Other South America	1,425 632	11,046	222	4,020	398	10, 33
Europe:	032	12, 210	867	16, 470	661	10, 47
Norway	2, 567	28, 087	11 Sec. 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1			
Sweden	10, 291	77, 458				
Switzerland	3, 591	31, 259				
United Kingdom	2, 120	37, 267				
Other Europe	2, 120					
Asia:	40	- 503	166	2,744		
China	563	6,060				
Japan	8.019	172, 860	3, 471			
Philippine Islands	2, 811	32, 653		60, 262		
Other Asia	123		4, 092	51, 359		
Oceania	143	2, 242				
Africa	39	787	10 500	290 5, 979	221	4, 949
					221	7, 840
	804, 095	5, 024, 992	708, 971	5, 389, 305	839, 582	6, 349, 801

Table 40.—Coke imported for consumption in the United States, 1940-42, by countries and customs districts

	19	940	19	<b>)41</b>	19	42
	Net tons	Value	Net tons	Value	Net tons	Value
COUNTRY				V		
CanadaMexico	77, 642	\$1, 114, 683	89, 677	\$1, 251, 417	97, 386	\$1, 221, 448
United Kingdom 1	34, 908	190, 457	178, 209	940, 512	7, 577 3, 819	85, 787 34, 449
	112, 550	1, 305, 140	267, 886	2, 191, 929	108, 782	1, 341, 684
CUSTOMS DISTRICT						
BuffaloConnecticut	47, 377	949, 150	48, 143 3, 793	1,023,849	51, 695	971, 499
El Paso Laredo				27, 880	6, 674 617	79, 919
Los Angeles	3, 035	13, 548	1,690	11 870		4, 660
Maine and New Hampshire Maryland	292 3, 390	2, 145 27, 241	342 107, 169	2,849 579,442	85	713
Massachusetts	14,091	74, 196	60,062	289, 517		
Michigan Montana and Idaho	10	74	. 9	76		
New York	26, 885 10, 782	141, 598	37, 339	201, 793	38,877	218, 241
St. Lawrence	10, 782	54, 888 446	3, 351	16, 752	3,819	34, 449
San Francisco	3, 611	20, 619	2, 143	15,051		
Vermont	291	2, 247	360	2,977		
Washington State	2, 721	18, 988	3, 485	19, 873	7, 015	32, 203
	112, 550	1, 305, 140	267, 886	2, 191, 929	108, 782	1, 341, 684

<sup>&</sup>lt;sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

### WORLD PRODUCTION

The following table shows world production of coke by countries in 1929 and 1939-42 to the limit of available statistics. Because of Government restrictions on the publication of statistics for many of the leading coke-producing countries, few figures have been available since 1939. However, as the output of iron and steel has since increased in most countries, doubtless the production of coke has also increased correspondingly. Production in both Canada and the United States has increased steadily during the past 4 years, and the 1942 output in these countries exceeded all previous production records.

Table 41.—Coke produced in principal countries of the world, 1929 and 1938-42, in metric tons 1 2

	, [Con	apiled by B. B	. Waldbauer	1		
Country 2	1929	1938	1939	1940	1941	1942
					444 22 11	
Australia:	4771 010	1, 153, 670	1, 370, 814	(3)	(3)	(3)
New South Wales Queensland	471, 813 4, 144	31, 481	31, 057	(3)	(3)	(3)
Belgium	6, 192, 960	4, 894, 980	5, 176, 650	(3)	(3)	(3)
Bulgaria	0, 102, 000	3, 923	4, 758	6,000	(3)	(3)
Canada	1, 986, 532	1, 808, 588	1, 830, 425	2, 321, 775	2, 431, 942	2, 795, 472
China (exports)	13, 467	11, 630	22, 562	18, 456	4 11, 918	(3)
China (exports) Czechoslovakia	3, 170, 629	5 2, 367, 000	(3)	(3)	(3)	(3)
France	9, 080, 127	7, 785, 000	(3)	(3)	(3)	(3)
Germany	39, 421, 033	3, 511, 082	(3)	(3)	(3)	(3)
Soor	2, 423, 000	) '				
Great Britain 6	13, 637, 421	13, 031, 396	(3)	(3) (3)	(3)	(3)
	2,092	53, 092	(3)	(3)	(3)	(%)
India, British 7	843, 504	1, 738, 178	1, 947, 455	(3)	(3) (3)	(3) (3)
Indochina	637	3, 503	4,022	2, 608	(3)	(3)
Italy	791, 607	1, 739, 417	(2)	(3)	(3)	(3)
Mexico	493, 777	(3)	8 2, 207, 501	8	3	(3)
Netherlands	2, 402, 566	3, 158, 065 49, 875	82, 100	69, 762	99, 700	83, 661
New Caledonia	35, 899	49, 810	(3)	(3)	(3)	(3), 002
PeruPoland	1, 858, 052	2, 523, 290	3	2	(3)	(3)
Rhodesia, Southern		47, 986	(3) 32, 785	(3)	(3)	(3)
Rumania	100,001	86,030	(3)	(3)	(3)	(3)
Spoin	768, 040	571, 469	685,000	839,744	767, 203	9 437, 426
SpainSweden	103, 778	112, 107	115, 150	(3)	(8)	(3)
Turkey	100,	84, 930	63, 472	60, 192	58, 642	(3)
Union of South Africa	99, 297	163, 315	184, 522	(3)	(3)	(3)
U. S. S. R.	4,700,000	20, 700, 000	16, 670, 000	16, 500, 000	(3)	(3)
United States	54, 325, 427	29, 479, 553	40, 212, 242	51, 774, 699	59, 135, 960	64, 018, 735
	142, 926, 000	135, 110, 000	(3)	(3)	(3)	(3)
			1	1		!

<sup>1</sup> Gas-house coke is not included.

In addition to countries listed, coke is produced in Chosen and Japan, but data of production are not

Incomplete figure (from coke plants of only 2 mines).
January to July, inclusive.
Exclusive of Mexico.

#### GAS-HOUSE COKE

The production of gas-house coke in the United States in 1942 totaled 892,552 net tons. The Bureau of Mines obtained data on the manufacture of coke from coal-gas retorts by a survey of this industry conducted at the request of the Office of Solid Fuels Coordinator for War. The survey showed that most of the gas-house

available.

3 Data not available.

4 January to August, inclusive.

5 Excluding Sudetenland since October.

6 In Great Britain the production of gas-house coke (including breeze), not included above, is especially mportant and was 13,049,139 tons in 1938.

7 Figures for 1929 represent "hard" and "soft" coke made at collieries only—73,616 tons of "hard" coke and 769,838 tons of "soft" coke. Data for other years shown represent total "hard" coke manufactured. In addition, the following quantities of "soft" coke were made at collieries: 1933, 921,479 tons; 1939, data not available. not available

coke was sold for domestic heating. Of the 533,882 tons sold, 449,220 tons was for domestic heating, 21,398 tons for water-gas manufacture, and 63,264 tons for miscellaneous industrial uses. The producers used 399,970 tons—206,864 tons for bench fuel, 123,851 tons for water-gas manufacture, 40,708 tons for boiler fuel, and 28,547 tons for the manufacture of producer gas. Table 42 gives salient statistics covering the operations of coal-gas retorts in the United States in 1942.

Table 42.—Salient statistics of the coal-gas industry in 1942 (coke, breeze, and coal figures in net tons)

	Horizontal retorts	Vertical retorts	Gas ovens	Total
Production:				
Coke	363, 358	509, 782	19, 412	892, 552
Breeze	38, 191	90, 782	3,002	131, 975
Coal charged into retorts	602, 623	886, 659	32, 330	, 521, 612
Average yield of coal charged: 1	002, 020	000,000	02, 000	, 021, 012
Cokepercent_	60, 30	57, 49	60, 04	58, 66
Breeze	8. 10	11.86	11.59	10.45
Number of active retorts	1,881	688	37	2, 606
Annual coal capacity of retorts	714, 037	1, 105, 202	68, 529	1, 887, 768
Coke used by producer.		1, 100, 202	00,020	1,001,100
For manufacture of water gas	35, 226	87, 627	998	123, 851
For manufacture of producer gas	00, 220	28, 547	800	28, 547
For bench fuel	97, 944	102, 970	5, 950	206, 864
For other purposes	28, 863	7, 117	4,728	40, 708
Coke sold to other consumers: For manufacture of water gas	20,000	1, 111	1,120	20, 100
For manufacture of water gas	5, 356	16, 042		21, 398
For domestic use	173, 941	264, 057	11, 222	449, 220
For other purposes	44, 934	18, 330	11, 222	63, 264
Stocks on hand Tonyony 1 1049:	11, 001	10,000		00, 201
Coke	45, 550	81, 829	3, 916	131, 295
Breeze	7, 201	20, 660	489	28, 350
Byproducts:	.,	20,000	1 200	20,000
Production:				
Targallons_	7, 366, 756	13, 440, 106	284, 967	21, 091, 829
Ammonia liquor (NH <sub>3</sub> content)pounds	106, 837	1, 383, 492	201, 001	1, 490, 329
	23, 793	68, 207		92,000
Used by producer:		00, 20.		. 02,000
Used by producer:  Tar  Ammonia liquor (NH2 content)  pounds	41, 665	72, 292		113, 957
Ammonia liquor (NH3 content)pounds_	,			220,000
Ammonia liquor (NH <sub>3</sub> content) pounds Crude light oil gallons	140			140
Sold to other congressions				
Targallons	6, 556, 546	13, 113, 393	317, 777	19, 987, 716
Ammonia liquor (NH2 content)pounds	133, 913	1, 372, 821		1, 506, 734
Crude light oil gallons	19, 109	62, 531		81, 640
Stocks on January 1, 1943:	**************************************			,
Targallons_	2, 407, 874	1, 542, 684	90, 739	4, 041, 297
Ammonis liquor (NH; content)pounds_ Crude light oilgallons_ Yield of byproducts per ton of coal: 1	7, 669	119, 758		127, 427
Crude light oilgallons_	6, 958	22, 131		29, 089
Yield of byproducts per ton of coal: 1	.,			
1 at 2 an one	12. 22	15. 16	8.81	13.86
Ammonia liquor (NH3 content)pounds_	1.72	3.45		3. 22
Crude light oil gallon	. 27	. 34		.32

<sup>&</sup>lt;sup>1</sup> Calculated on coal charged at plants actually recovering

はいけん 最上 大きまる

Table 43.—Coke produced, number of retorts, coal charged, and average yield at coal-gas plants in 1942, by States

State	Num- ber of active plants	Num- ber of active retorts	Coal capacity per 24- hour day (net tons)	Coal used (net tons)		Coke pro- duced (net tons)	Coke sold (net tons)	Coke used (net tons)	Coke stocks on Jan- uary 1, 1943 (net) tons)
Alabama and Kentucky	3	30	27	7, 693	53. 13	4, 087	1, 294	2, 493	514
Colorado and North Da- kota	4	46	70.6	22, 790	59.78	13, 625	8, 332	5, 363	3, 460
VermontGeorgiaIllinois, Indiana, and	6	1 95 48	502.1 45.96	142, 194 12, 733	57. 31 50. 16	81, 488 6, 387	46, 118 4, 278	37, 467 3, 077	16, 332 330
Inmois, Indiana, and Iowa Maryland, Virginia, and	5	69	143.4	33, 560	58. 69	19, 697	18,068	6, 358	749
West Virginia Massachusetts	4 10	56 382	134. 5 1, 214. 72	44, 516 427, 336	64. 55 55. 26	28, 733 236, 151	19, 243 119, 301	11, 074 108, 075	2, 245 56, 325
MichiganMinnesota	19 4	2 263 75	322.97 67.5	98, 219 19, 523	64. 54 59. 66	63, 392 11, 647	43, 728 8, 316	23, 996 4, 698	10, 500
New Jersey, New York, and Ohio	6	268	634.45 358.1	129, 334	65. 25 58. 89	84, 387 58, 175	52, 161 32, 133	24, 941 31, 163	18,75
North Carolina Pennsylvania South Carolina	10 5 3	306 144 126	278.65 144.4	98, 790 91, 404 39, 047	64. 91 58. 22	59, 335 22, 735	1, 492 11, 407	57, 397 12, 470	5, 640 58 1, 85
Tennessee	3	270 156	240.12 101.88	73, 416 32, 970	60. 50 59. 42	44, 419 19, 592	26, 996 11, 580	19, 346 12, 411	1,35
Wisconsin	8	272	885. 615	248, 087	55. 91	138, 702	129, 435	39, 641	10, 110
	96	2, 606	5, 171. 965	1, 521, 612	58.66	892, 552	533, 882	399, 970	131, 29

<sup>&</sup>lt;sup>1</sup> Includes 15 horizontal gas ovens.

#### COKE-OVEN BYPRODUCTS

#### SUMMARY OF BYPRODUCTS

Rivaling the coke in importance and in volume of production but more versatile in the forms in which they are used are the byproducts. The volatile matter resulting from the carbonization process is processed to produce the four major byproducts—tar, ammonia, light oil, and gas-by preferential condensation and absorption operations. Initial cooling upon leaving the carbonizing chamber results in the condensation of the heavier higher-boiling-point constituents comprising the coal tar; further cooling with water or scrubbing with sulfuric acid effects recovery of the ammonia as an aqueous solution or in the form of ammonium sulfate; and still further cooling, followed by oil washing, strips out the light oils, consisting mainly of benzol, toluol, xylol, solvent naphtha, and naphthalene. After this point only the gas remains in the system as the final primary product. The further processing of some of the major byproducts involves many chemical industries. Here finished products consist of a host of chemical products, such as dyes, pharmaceuticals, plastics, explosives, and synthetic rubber goods, all of which are indispensable in peace and war.

The acceleration in the rate of coke-oven operation in 1942 increased substantially the production of the byproducts and thereby increased their total sales value. The total sales of all byproducts sold in 1942 (excluding the value of the tar used by the producers and the value of coke breeze produced) increased 11 percent from \$158,809,184 in 1941 to \$176,932,465 and amounted to 47 percent of the gross value of the coke produced. This was a slight decrease from the 1941 ratio and was caused by the price adjustments of coke and byproducts. The

<sup>&</sup>lt;sup>2</sup> Includes 22 horizontal gas ovens.

yields of the primary coke byproducts per ton of coal carbonized declined in 1942 from that in 1941 because of more rapid coking rates

(fig. 2).

Gas.—Coke-oven gas contributed approximately 50 percent of the total revenue derived from the sales of all byproducts. In addition to providing the fuel requirements of the byproduct ovens from which it is evolved, coke-oven gas supplied other fuel needs. In 1942, 585,455,085 M cubic feet (62 percent) of the 944,879,637 M cubic feet produced were used or sold for industrial purposes and for distribution through city mains. The total value of the gas so used rose from




Figure 2.—Average yield of principal byproducts per net ton of coal carbonized in byproduct-coke ovens, 1915-42. Figures for light oil represent average at plants recovering light oil.

\$85,040,609 to \$88,823,807; however, the average sales value as reported by the operators dropped from \$0.153 per M cubic feet in 1941 to \$0.152 in 1942.

Tar.—The importance of tar as a commercial product has been emphasized during the past year more than ever before. During 1942 the market for tar and its derivatives increased sharply, since the tar derivatives are the basic raw materials from which many products essential to war industries and to public health are made. The diminishing consumption of tar as a fuel in metallurgical works is shown by the increased quantities available each year for refining. The quantity of tar refined by the producers and sold for refining increased 16 percent in 1942 and rose from 458,334,224 to 533,597,898 gallons. In addition, 104,101,925 gallons of crude tar were topped. "Topping" is designed primarily to strip the light oil and tar-acid oil

fractions from the crude tar, and in some plants even higher fractions by mild refining. Crude tar, used as fuel by producers and sold for use as fuel, decreased sharply and dropped from 154,065,404 in 1941 to 98,154,832 gallons in 1942. The sales of crude tar in 1942 amounted to 445,597,291 gallons, of which 443,007,596 gallons (99 percent) were sold for refining into tar products and 2,589,695 gallons for fuel. average unit price of the crude coal tar sold in 1942 rose \$0.007 and

reached \$0.054 per gallon.

Ammonia.—Byproduct-coke ovens are the most important source of fertilizer nitrogen in the United States. The relatively low conversion costs and the large demands for sulfate by the fertilizer industry account for the fact that most of the ammonia recovered from coke ovens is converted to ammonium sulfate. In 1942, 1 533,-608,185 pounds of ammonium sulfate and 67,854,384 pounds of ammonia in the form of liquor were produced compared with the 1941 figure of 1,490,395,760 and 62,777,031 pounds. The average unit value of ammonium sulfate remained the same as for the previous year at \$0.013 per pound and was governed by Maximum Price Regulation 205.

Light oil and its derivatives.—The primary product, light oil, and its components are extensively used in the chemical industries. production of crude light oil in 1942 increased 6 percent over 1941 and totaled 246,024,882 gallons. The majority of the byproductcoke plants have refining equipment adjacent to the ovens, and the light oil is processed on the premises. Of the total production, 241,854,110 gallons (98 percent) were refined by the producers, and only 14,915,409 gallons were sold as crude light oil.

The issuance of War Production Board General Preference Order M-137, effective July 1, 1942, prohibited the use of benzol in motor fuel and placed it under complete allocation. In previous years most of the benzol produced was motor benzol; however, the acute need for industrial pure or 2° benzol by the war industries that manufacture aviation gasoline, synthetic phenol, aniline, and other finished products resulted in issuance of this order. In 1942 the production of motor benzol decreased 40,267,397 gallons, but the production of crude and refined benzol, principally 1° and 2°, increased 46,066,495 gallons. The production of toluol, another major derivative of light oil advenced from 20,227,179 to 20,214,500 ml. light oil, advanced from 29,337,178 to 32,314,560 gallons (10 percent), and practically all of it was used for explosives. Toluol had been under allocation since August 1941, following the issuance of the War Production Board General Preference Order M-34 on August 8, 1941.

Naphthalene.—Naphthalene is an important byproduct of coal carbonization. It is solid crystalline hydrocarbon and is obtained principally by cooling coal-tar oils, which boil between 170° and 230° Naphthalene is used in the manufacture of phthalic anhydride for smokeless powder, alkyd resins, dyestuffs, perfumes, medicinal insecticides, and moth preventatives. Naphthalene grades are defined in terms of melting points, 79° C. being the dividing line between pure and crude grades. In view of increasing requirements, the byproduct-coke-plant operators increased the output of this valuable byproduct, and production in 1942 rose to 95,612,788 pounds compared with the 1941 figure of 84,046,676 pounds—an increase of 14 percent. The sales of naphthalene increased in propertion to the production, and the value totaled \$1,941,626—an increase of \$419,108 (28 percent). Naphthalene was placed under allocation on May 6, 1942, following issuance of the War Production Board General Preference Order M-105.

Table 44.—Byproducts obtained from coke-oven operations in the United States in 1942 1

#### [Exclusive of screenings or breeze]

Product	Production		Value	On hand Decem-	
		Quantity	Total	Aver- age	ber 31
Targallons	740, 175, 619	445, 597, 291	\$24, 155, 601	\$0.054	31, 738, 564
Ammonia: Sulfatepounds Liquor (NH; content)do	1, 533, 608, 185 67, 854, 384	1, 503, 828, 945 63, 875, 140	19, 460, 205 2, 238, 367	. 013	87, 352, 849 2, 031, 142
Sulfate equivalent of all forms do NH3 equivalent of all forms do	1, 805, 025, 721 451, 256, 430	1, 759, 329, 505 439, 832, 376	21, 698, 572		05 477 417
Gas:  Used under boilers, etcM cubic feetUsed in steel or affiliated plantsdo Distributed through city mainsdo Sold for industrial usedo	2 944,879, 637	49, 414, 260 335, 290, 705 169, 530, 544 31, 219, 576	34, 935, 356 45, 782, 434	270	
모든 함께 없는 모든 모든 모든 그릇을 다 했다.	2 944, 879, 637	585, 455, 085	88, 823, 807	. 152	
Light oil and derivatives:      gallons         Crude light oil      gallons         Benzol, crude and refined      do         Motor benzol      do         Toluol, crude and refined      do         Xylol      do         Solvent naphtha      do         Other light oil products      do	85, 256, 998 64, 797, 595 32, 314, 560 9, 332, 273 5 215 617	80, 778, 763 62, 854, 535 32, 182, 327 8, 868, 817 5, 067, 935	10, 487, 450 5, 389, 540 8, 536, 446 -2, 219, 991 726, 247	. 084 . 130 . 086 . 265 . 250 . 143 . 091	4, 978, 004 1, 759, 602 1, 005, 966 550, 530 341, 383
Naphthalene, crude and refinedpounds. Tar derivatives:			29, 293, 280 1, 941, 626	. 138	2, 648, 546
Creosote oil, distillate as such gallons. Creosote oil in coal-tar solution do. Tar acid oil do Phenol, crude and refined do. Pitch of tar net tons	3, 172, 731 17, 921, 998 1, 019, 808 638, 158	1, 299, 576 11, 340, 244 1, 017, 762	4, 651, 761 185, 055 1, 555, 882 768, 926 114, 504	. 118 . 142 . 137 . 756 13, 339	2, 440, 749 34, 826 661, 794 4, 366 39, 737
Other tar derivatives. Light carbolic oil	1, 858, 928	1, 816, 207 485, 552 4, 258, 481	2, 211, 509 229, 225 634, 358 249, 465 418, 894		64, 418 126, 912
Value of all byproducts sold			6 176,932, 465		

<sup>1</sup> Includes products of tar distillation conducted by coke-oven operators under same corporate name.
2 Includes gas wasted and gas used for heating ovens.
3 Refined on premises to make the derived products shown: 241,854,110 gallons.
4 Total gallons of derived products.
5 Ammonia thiocyanate, cyanogen, dicycloentadiene, phenol from sources other than tar distillation, picoline, sal ammoniac, sodium prussiate, spent soda ash solution, sulfur, vented vapors, and residue.
5 Exclusive of value of breeze production, which was \$10,897,121 in 1942.

Table 45.—Coal equivalent of byproducts of byproduct coking in the United States, 1913, 1914, 1918, and 1941–42

Quantity of byproducts				Rough e	quivalen	Coal equivalent					
	(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
Year	Coke breeze (thou- sand net tons)	Surplus gas (bil- lion cubic feet)	duced (thou-	Light oil pro- duced (thou- sand gallons)	Coke breeze (1 x 20)	Surplus gas (2 x 550)	Tar (3 x 0.150)	Light oil (4 x 0.130)	Total (5+6+ 7+8)	Net tons (9÷ 0.0262)	Percent this forms of coal made into coke
1913	735 667 1, 999 4, 433 4, 600	61 158 554	109, 901 263, 299 704, 149	8, 464 87, 562 231, 359	13, 340 39, 980 88, 660	33, 550 86, 900 304, 700	17, 272 16, 485 39, 495 105, 622 111, 026	1, 100 11, 383 30, 077		2, 461, 000	4. 8 8. 0 21. 7

## COKE-OVEN GAS

Table 46.—Coke-oven gas produced and sold in the United States in 1942, by States

				Surpl	us sold or u	sed	
State	Active plants		Used in heating ovens (M	M cubic	Valu	Wasted (M cubic feet)	
		1000	cubic feet)	feet	Total	Aver- age	
Alabama Colorado Illinois Indiana Maryland Massachusetts Michigan Minnesota Menyland Minnesota Moresey New York Ohio Pennsylvania Tennessee Utah West Virginia Connecticut, Kentucky, Missouri, Rhode Island, and Wisconsin	1 9 5 1 2 7 3 2 8 15 14 1 1 1 5	108, 155, 676 26, 315, 747 18, 390, 302 48, 190, 216 13, 784, 317 16, 354, 789 78, 491, 881 143, 321, 823 262, 615, 454 3, 098, 605 2, 265, 925 39, 186, 622	6, 202, 494 15, 506, 573 44, 475, 612 9, 783, 301 3, 993, 933 5, 811, 707 3, 353, 573 21, 184, 788 60, 881, 437 106, 219, 892 1, 366, 071 2, 328, 957	5, 964, 084 34, 380, 676 62, 746, 234 16, 064, 326 14, 339, 572 41, 212, 476 7, 821, 718 13, 001, 216 56, 891, 882 7, 305, 715 154, 305, 715 26, 753 28, 101, 587	4, 508, 067 11, 598, 599 (1) 5, 071, 299 1, 745, 263 (1) 16, 699, 455 8, 654, 467 17, 165, 770 (1) 2, 355, 758	. 223 (1) . 294 . 112 . 111 (1) (1) . 084	158, 474 784, 876 933, 830 468, 120 56, 791 165, 203 150, 892
UndistributedGrand total, 1942			344, 412, 807		11, 022, 302	. 206	
At merchant plantsAt furnace plants	42	224, 425, 460	54, 402, 790 290, 010, 017	163, 322, 088	40, 664, 004	. 249	6, 700, 582
Grand total, 1941	87	89 <b>2,</b> 819, 811	328, 137, 246	554, 126, 449	85, 040, 609	. 153	10, 556, 116

<sup>1</sup> Included under "Undistributed."

Table 47.—Disposal of surplus coke-oven gas in the United States in 1942, by States .

		τ	Jsed by 1	producer—		Sold						
<b>0</b> 1. II	Uı	der boilers		In steel or other affiliated plants			Distributed	l through cit	y mains	Sold for industrial purposes		
State	M cubic	Valu	ıe	M cubic	Value		M cubic	Value		M cubic	Value	
	feet	Total	Average	feet	Total	Average	feet	Total	Average	feet	Total	Average
AlabamaColorado	8, 504, 879	\$402,082	\$0.047	26, 248, 173 5, 964, 084	\$2, 375, 732	\$0.091	6, 602, 717	\$701,092	\$0.106	2, 457, 827	\$228, 447	\$0.093
Indiana	2, 631, 427 3, 175, 229	209, 466 257, 373	.080 .081	5, 855, 471 49, 890, 021 8, 987, 904	903, 274 6, 758, 456	. 154 . 135	23, 015, 131 7, 643, 947 7, 076, 422	3, 108, 250 3, 869, 807	.135	2, 878, 647 2, 037, 037	287, 077 712, 963	. 100
Maryland Massachusetts Michigan Minnesota	3, 035 6, 947, 587 1, 583, 910	(1) 831, 649 133, 128	(¹) .120 .084	27, 889, 308 1, 852, 165	3, 290, 314 229, 115	(1) . 118 . 124	14, 200, 092 1, 958, 108 4, 385, 643	(1) 319, 532 1, 383, 020	(1) (1) . 163 . 315	135, 777 4, 417, 473	(1) 629, 804	(1) . <b>14</b> 8
New Jersey New York Ohio Pennsylvania Pennessee	2, 300, 016 4, 436, 292 6, 146, 797 449, 650	190, 664 411, 814 571, 696	. 083 . 093 . 093 (1)	284 11, 292, 120 60, 296, 114 120, 714, 286	1, 094, 357 6, 101, 842 11, 071, 951	.097 .101 .092	13,000,932 40,627,275 8,165,946 19,874,343 1,089,229	14, 973, 578 1, 620, 360 4, 796, 304	(1) . 369 . 198 . 241	2, 672, 471 4, 610, 383 7, 570, 068	440, 856 520, 451 725, 819	. 168 . 113 . 096
Utah West Virginia_	1, 696, 354 9, 791, 784	(1) 672, 418	.069	77, 377 16, 222, 730	(1) 1, 412, 455	(1) . 087	664, 665	(1) (1)	(1) (1)	198, 357 2, 087, 073	(1) 270, 885	(¹) .130
Connecticut, Kentucky, Missouri, Rhode Island, and Wisconsin Undistributed	1,747,300	150, 432 159, 994	.086 .074		1, 697, 860	.113	21, 226, 114	5, 905, 148 9, 105, 343	. 278 . 253	2, 154, 463	239, 894 59, 105	. 111 . 177
Grand total, 1942	49, 414, 260	3, 990, 716	. 081	335, 290, 705	34, 935, 356	. 104	169, 530, 544	45, 782, 434	. 270	31, 219, 576	4, 115, 301	. 132
At merchant plants At furnace plants	21, 892, 848 27, 521, 412	1, 610, 895 2, 379, 821	.074	2, 110, 736 333, 179, 969	294, 162 34, 641, 194	.139	120, 185, 225 49, 345, 319	35, 854, 767 9, 927, 667	. 298	19, 133, 279 12, 086, 297	2, 904, 180 1, 211, 121	. 152
Grand total, 1941	31, 404, 684	2, 365, 659	. 075	330, 452, 000	34, 448, 880	. 104	159, 746, 453	44, 108, 797	. 276	32, 523, 312	4, 117, 273	. 127

<sup>1</sup> Included under "Undistributed."

TAR Table 48.—Coke-oven tar produced and sold in the United States in 1942, by States

	Produced 1 (g	ced <sup>1</sup> (gallons)						Used b			
( State	Total	Per ton of coal coked	For use as fuel <sup>3</sup> (gallons)	For refining into tar products (gallons)	Gallons	Total V: Total	Aver-	As fuel under boilers	In open- hearth or affiliated plants	Otherwise	On hand December 31 (gallons)
Alabama Colorado Illinios Indiana Maryland Massachusetts. Michigan Minnesota New Jersey New York. Ohio Pennsylvania Tennessee Utah West Virginia Connecticut, Kentucky, Missouri, Rhode Island, and Wisconsin Undistributed	65, 869, 866 10, 716, 805 38, 819, 743 61, 509, 465 22, 676, 636 12, 884, 647 34, 640, 046 8, 461, 949 11, 712, 216 64, 441, 849 105, 975, 336 234, 531, 227 2, 369, 894 4, 512, 437 36, 780, 326 24, 274, 277	8. 47 10. 50 7. 43 6. 06 7. 81 7. 72 7. 95 6. 66 8. 14 8. 88 7. 72 9. 82 7. 18 11. 14 10. 50 7. 98	140, 535 357, 861 50 2, 091, 147 102	44, 596, 096 214, 054 29, 713, 290 43, 785, 114 20, 056, 159 13, 154, 237 34, 583, 816 8, 511, 731 12, 092, 576 51, 513, 097 90, 134, 094 27, 461, 900 2, 343, 964 4, 527, 076 36, 319, 703 24, 000, 689	44, 596, 096 214, 054 29, 713, 290 43, 925, 649 20, 056, 159 13, 154, 237 34, 583, 816 8, 511, 731 12, 092, 576 51, 870, 958 90, 134, 144 29, 553, 047 2, 343, 964 4, 527, 78 36, 319, 703 24, 000, 689	\$2, 627, 238 (4) 1, 601, 264 1, 978, 541 (5) 1, 778, 968 505, 762 (2, 910, 293 5, 053, 420 1, 573, 815 (4) 2, 049, 387 1, 274, 036 2, 803, 877	\$0.059 (4) .054 .045 (4) .059 (5) .056 .053 (4) .056 .056	265, 797 446 617, 853 293, 849	911, 484 11, 109, 424 58, 285, 280	305, 805 110 1, 023, 620 47, 718 2, 436 66, 571 220, 763 3, 205 655	2, 465, 530 296, 159 1, 790, 771 2, 977, 666 2, 810, 338 196, 096 1, 282, 653 419, 359 262, 100 3, 483, 743 4, 311, 939 9, 239, 924 49, 792 160, 008 1, 040, 446
Grand total, 1942	740, 175, 619	8. 41	2, 589, 695	443, 007, 596	445, 597, 291	24, 155, 601	.054	1, 177, 945	94, 387, 192	1, 670, 873 102, 195	31, 738, 564 5, 919, 443
At merchant plants	179, 956, 343 560, 219, 276 704, 149, 468	8. 59 8. 36 8. 52	309, 807 2, 279, 888 14, 749, 274	169, 741, 341 273, 266, 255 377, 790, 519	170, 051, 148 275, 546, 143 392, 539, 793	9, 066, 585 15, 089, 016 18, 386, 170	. 053	1, 177, 945 3, 225, 550	94, 387, 192 136, 090, 580	1, 568, 678 1, 401, 067	25, 819, 121

<sup>&</sup>lt;sup>1</sup> Includes 90,590,302 gallons of tar "refined at plant" and 104,101,925 gallons of tar "topped."

<sup>2</sup> Excludes 90,590,302 gallons of tar "refined at plant" and 104,101,925 gallons of tar "topped."

<sup>3</sup> Comprises 395,450 gallons of tar sold to affiliated corporations and 2,194,245 gallons sold to other purchasers.

<sup>4</sup> Included under "Undistributed."

<sup>5</sup> Revised figure.

# AMMONIA Table 49.—Coke-oven ammonia produced and sold in the United States in 1942, by States

		Sulfate equiv		Produ	ced as—		Sold	as—		On hand Do	
State	Active plants	Total	Per ton	Sunate	Liquor (NH <sub>3</sub>	Sulf	ate	Liquor (N	H <sub>3</sub> content)		Liquor
	·	10021	coked	(pounds)	(pounds) content) (pounds)	Pounds	Value	Pounds	Value	Sulfate	(NH <sub>3</sub> content)
AlabamaColorado	8	186, 939, 287 23, 665, 332	24.03 23.18	159, 143, 535 23, 665, 332	6, 948, 938	154, 513, 244 22, 127, 312	\$2, 104, 800	7, 056, 766	\$275, 914	5, 572, 258 3, 640, 000	66, 559
Illinois Indiana Maryland Massachusetts	7 5 1	95, 466, 198 173, 475, 476 50, 430, 800	19.10 17.10 17.36	74, 304, 414 151, 570, 132 50, 430, 800	5, 290, 446 5, 476, 336	74, 440, 267 161, 438, 918 50, 658, 600	909, 601 2, 011, 857	5, 313, 732 5, 506, 296	(1) (1)	3, 373, 380 1, 936, 466 1, 472, 200	81, 011 163, 003
Michigan Minnesota	7	30, 859, 968 92, 549, 331 22, 620, 012	18. 49 21. 23 17. 80	27, 056, 000 32, 999, 499 22, 620, 012	950, 992 14, 887, 458	26, 652, 000 35, 347, 980 22, 610, 595	(1) (1) (1) 267, 607	949, 192 12, 500, 139	308, 921	690,000 23,575 2,049,032	18, 042 553, 715
New York	. 2	29, 342, 234 148, 989, 829 280, 434, 134	20. 39 20. 53 20. 42	29, 342, 234 118, 106, 005 223, 582, 802	7, 720, 956 14, 212, 833	28, 787, 070 115, 797, 020 221, 520, 645	1, 604, 010 2, 740, 824	7, 706, 391 12, 832, 768	299, 490 496, 502	949, 828 7, 352, 881 5, 918, 285	132, 997 376, 887
Ohio Pennsylvania Tennessee Utah	13 1 1	533, 724, 262 6, 412, 272 11, 069, 740	22. 43 19. 44 27. 32	526, 823, 974 6, 412, 272 11, 069, 740	1,725,072	496, 390, 399 6, 500, 680 10, 735, 675	6, 323, 851 (1) (1)	1, 641, 405	65, 216	51, 714, 615 86, 239 1, 435, 764	46, 799
West Virginia. Connecticut, Kentucky, Missouri, Rhode Island, and Wisconsin	3	55, 081, 872 63, 964, 974	22, 54 21, 04	55, 081, 872 21, 399, 562	10, 641, 353	54, 799, 530 21, 509, 010	697, 969 295, 109	10, 368, 451		637, 770	
Undistributed Grand total, 1942	82	1, 805, 025, 721		1, 533, 608, 185		1, 503, 828, 945	2,504,577		420, 396		592, 129
At merchant plantsAt furnace plants	36	416, 541, 607	21.33	232, 473, 491	46, 017, 029	231, 671, 335	3, 202, 382	63, 875, 140 41, 996, 167	2, 238, 367 1, 557, 778	87, 352, 849 8, 886, 183	2, 031, 142 1, 757, 298
Grand total, 1941		1, 388, 484, 114 1, 741, 503, 884		1, 301, 134, 694 1, 490, 395, 760		1, 272, 157, 610 1, 513, 137, 970	16, 257, 823	21, 878, 973 60, 341, 804	2,000,973	78, 466, 666 62, 182, 393	273, 844 1, 513, 180

<sup>1</sup> Included under "Undistributed."

#### LIGHT OIL AND ITS DERIVATIVES

Table 50.—Coke-oven crude light oil produced in the United States and derived products obtained and sold in 1942, by States

		Produced	(gallons)	D.64	Derived p	roducts obt sold	ained and	On hand	
State	Active plants		Per ton	Refined on premises (gallons)	Produced	Sol	Decem- ber 31 (gallons		
		·	coked		(gallons)	Gallons	Value		
Alabama Colorado Illinois	8 1 5	22, 378, 246 3, 063, 002 11, 573, 875	3.00	3, 058, 450	2, 844, 646	2, 779, 893		129, 455	
Indiana Maryland Michigan	4 1 4	23, 064, 655 10, 431, 365 12, 237, 878	2. 44 3. 59 2. 94	24, 782, 790 10, 409, 584 6, 854, 856	21, 748, 646 8, 682, 447 6, 195, 667	21, 157, 966 8, 371, 240 4, 854, 559	2, 979, 188 (2) 705, 136	613, 420 586, 511 146, 338	
New York Ohio Pennsylvania Tennessee	8 15 13 1	75, 258, 010	2.91 3.16	34, 852, 189 74, 253, 947	28, 152, 365 63, 674, 869	27, 445, 479 60, 821, 821	3, 763, 315 8, 472, 368	1, 257, 271 2, 819, 419	
Utah	i 4	694, 228 1, 690, 520 9, 908, 249	4.17		1, 189, 670		(2)	62, 604 73, 842 320, 502	
tucky, Massachu- setts, Minnesota, Missouri, New									
Jersey, and Wisconsin	9	15, 728, 818	2.34	11, 018, 309	9, 547, 786	9, 281, 650	1, 482, 688 1, 652, 203	583, 266	
Grand total, 1942	74	246, 024, 882	2. 88	241, 854, 110	206, 155, 160	197, 261, 798	28, 046, 207	8, 818, 153	
At merchant plantsAt furnace plants		48, 625, 969 197, 398, 913		49, 414, 608 192, 439, 502		39, 810, 457 157, 451, 341			
Grand total, 1941	70	231, 358, 897	2. 90	225, 294, 298	194, 713, 669	193, 011, 869	22, 824, 574	5, 135, 095	

Excludes 14,915,409 gallons, valued at \$1,247,073, of crude light oil sold as such. Included under "Undistributed."

#### NAPHTHALENE

Table 51.—Crude and refined naphthalene sold by byproduct-coke operators in the United States, 1938-42

			Val	ue	
	Year	Pounds	Total	Average receipts per pound (cents)	Receipts per ton of coke (cents
1938		25, 456, 400 46, 551, 432 72, 522, 476 83, 879, 396 95, 039, 639	\$437, 654 727, 947 1, 248, 051 1, 522, 518 1, 941, 626	1.7 1.6 1.7 1.8 2.0	1. 2. 2. 2. 3.

## BYPRODUCT-COKE OVENS OWNED BY CITY GAS COMPANIES (PUBLIC UTILITY PLANTS)

The adaptability of byproduct ovens to the needs of city gas manufacture has led a number of gas companies to install batteries of byproduct ovens to supplement or even replace coal- or water-gas sets. Although more emphasis is placed upon the production of gas of proper analysis than upon the grade of coke obtained, viewed from supply and demand for coke and byproducts, these installations belong to the byproduct-coke industry and are therefore included in the current statistics compiled by the Bureau of Mines and released to the public in weekly and monthly reports. The difference in classification is maintained in the interest of those who may want to obtain information on the operations of city gas works proper. Table 52 shows separate figures for the group of byproduct-coke plants operated by city gas companies (Public Utilities) and for all other byproduct-coke plants. In 1942, there were 16 active plants in the group owned by city gas companies and they produced 3,693,407 tons of coke, 59,480,526 M cubic feet of gas, 48,548,754 gallons of tar, and 7,973,417 gallons of light oil. This was an increase of 9 percent for coke, 6 percent for gas, 6 percent for tar, and 28 percent for light oil. This table also shows the operations of the plants not owned by city gas companies, which in 1942 produced 58,601,502 tons of coke, 885,-399,111 M cubic feet of gas, 691,626,865 gallons of tar, and 238,051,465 gallons of crude light oil.


Table 52.—Production of coke, breeze, gas, and byproducts in the United States at byproduct-coke plants owned by city gas companies (public utilities) and at all other byproduct-coke plants, 1941-42

		1941			1942	
Product	Plants not owned by city gas companies	Plants owned by city gas companies (public utilities) <sup>1</sup>	Total*	Plants not owned by city gas companies	Plants owned by city gas companies (public utilities) <sup>1</sup>	Total
Number of active plants	71	16	87	72	16	88
Coke: Productionnet tons_ Value Average	55, 079, 048 \$291, 628, 638	\$24, 848, 593	\$316, 477, 231	\$348, 619, 972	\$29, 391, 995	62, 294, 909 \$378, 011, 967
Screenings or breeze: Productionnet tons_	\$5, 29 4, 146, 242		\$5. 41 4, 432, 864	\$5, 95 4, 329, 511		\$6.07
Salesdo Value	804, 324 \$1, 930, 149	31, 835 \$84, 411	836, 159 \$2, 014, 560	912, 652 \$2, 495, 558	19, 470 \$60, 427	932, 122 \$2, 555, 985
Average  Coal charged into ovens:  Quantity net tons	\$2.40 77,763,252		1 1			• • • • • •
Coke: Used by producer:	11, 100, 202	4, 040, 000	02,000,001	02, 149, 094	0, 224, 127	87, 973, 821
Quantitynet tons Value	40, 416, 930 \$196, 417, 684	1, 113, 468 \$7, 051, 283	41, 530, 398 \$203, 468, 967	43, 135, 628 \$238, 573, 063		
Sales: Quantitynet tons_ Value Byproducts:	14, 747, 208 \$96, 481, 516	2, 403, 881 \$18, 619, 617	17, 151, 089 \$115, 101, 133	15, 522, 951 \$110, 614, 001	2, 582, 992 \$22, 117, 108	18, 105, 943 \$132, 731, 109
Gas: ProductionM cu. ft Sales of surplus: Used under boilers:	836, 747, 586	56 <b>, 072, 22</b> 5	892, 819, 811	885, 399, 111	59, 480, 526	944, 879, 637
Quantity M cu. ft. Value Used in steel or affiliated plants:	31, 368, 112 \$2, 357, 378		31, 404, 684 \$2, 365, 659	49, 403, 214 \$3, 987, 367	11, 046 \$3, 349	49, 414, 260 \$3, 990, 716
Quantity_M cu. ft Value Distributed through	330, <b>443,</b> 993 \$34, <b>44</b> 6, <b>47</b> 8	8, 007 \$2, 402	330. 452, 000 \$34, 448, 880	335, 290, 705 \$34, 935, 356		335, 290, 705 \$34, 935, 356
city mains: Quantity_M cu. ft Value Sold for industrial use:	110, 054, 651 \$26, 565, 768		159, 746, 453 \$44, 108, 797		52, 349, 122 \$18, 480, 535	169, 530, 544 \$45, 782, 434
Quantity_M cu. ft Value	29, 820, 721 \$3, 293, 920		32, 523, 312 \$4, 117, 273	27, 660, 835 \$2, 994, 472		31, 219, 576 \$4, 115, 301
Tar: Productiongallons Sales:	658, 263, 692	45, 885, 776	704, 149, 468	691, 626, 865	48, 548, 754	740, 175, 619
Quantitydo Value Average	345, 358, 272 \$16, 185, 453 \$0. 047	\$2, 200, 717	392, 539, 793 \$18, 386, 170 \$0. 047	397, 409, 041 \$21, 595, 088 \$0. 054		445, 597, 291 \$24, 155, 601 \$0. 054

<sup>&</sup>lt;sup>1</sup> Includes all byproduct ovens built by city gas companies, some of which are operated in conjunction with coal, oil, and water-gas plants. Does not include independent byproduct plants, which may sell gas to public utility companies for distribution.

Table 52.—Production of coke, breeze, gas, and byproducts in the United States at byproduct-coke plants owned by city gas companies (public utilities) and at all other byproduct-coke plants, 1941–42.—Continued

		1941			1942	
Product	Plants not owned by city gas companies	Plants owned by city gas companies (public utilities) <sup>1</sup>	Total	Plants not owned by city gas companies	Plants owned by city gas companies (public utilities)	Total
Ammonia: Production (NH <sub>3</sub> equivalent of all forms)						
pounds	410, 834, 145	24, 541, 826	435, 375, 971	426, 031, 332	25, 225, 098	451, 256, 430
Liquor (NH3 content):	FO FOO 004	0 100 105	00 555 001	04 100 004	0 050 000	67 054 00
Productionpounds Salesdo	59, 596, 924 57, 167, 866					
Value	\$1, 930, 241		\$2,000,973			
Sulfate:	41, 500, 211	ψ10, 10 <u>2</u>	42,000,010	Ψ2, 101, 000	φ101, 002	ψ2, 200, 00.
Production pounds_	1, 404, 948, 883	85, 446, 877	1, 490, 395, 760	1, 447, 332, 033	86, 276, 152	1, 533, 608, 18
Salesdo			1, 513, 137, 970			1, 503, 828, 94
Value	\$18, 499, 497	\$1, 209, 149	\$19, 708, 646	\$18, 247, 787	\$1, 212, 418	\$19, 460, 20
Crude light oil:	005 150 050	0 000 000	001 050 005	000 051 405	7 079 417	040 004 000
Productiongallons	225, 150, 258 8, 750, 082					
Salesdo	\$650,603					\$1, 247, 07
Light oil derivatives:	\$000,000	φ100, 021	4011, 221	ψ1, 010, 002	φ200, 001	ψ2, <b>2</b> 21, 01.
Production gallons	189, 652, 682	5,060,987	194, 713, 669	199, 097, 945	7, 057, 215	206, 155, 160
Salesdo	187, 898, 957		193, 011, 869			
Value	\$22,063,964			\$26, 929, 688	\$1, 116, 519	\$28, 046, 20
Naphthalene, crude and re-			Maria Barana			
fined:	00 001 700	FFF 100	04 040 070	04 450 495	1 100 252	AF 610 70
Productionpounds_	83, 291, 568					95, 612, 78 95, 039, 63
Salesdo	83, 140, 313 \$1, 511, 176		\$1,522,518			\$1, 941, 62
All other byproducts, value.			\$8, 481, 467		\$75, 121	\$11, 019, 57



## FUEL BRIQUETS AND PACKAGED FUEL 1

By G. S. GOODMAN AND G. E. CARLSON

#### SUMMARY OUTLINE

	Page		Page
Summary	1005	Fuel briquets—Continued.	
Technologic developments	1006	Distribution	1013
Fuel briquets	1006	Imports and exports	1014
Salient statistics	1007	World production	1015
Production	1008	Packaged fuel	1015
Value	1009	Processes	1016
Prices	1010	Salient statistics	1016
Number of plants	1010	Production and value	1016
Size of plants	1011	Number of plants	1018
Raw fuels	1011	Size of plants	1018
Binders	1012	Raw fuels	1019
Weight and shape	1013	Binders	1019

#### SUMMARY

Notwithstanding difficulties resulting from the war in securing raw fuel, labor, and miscellaneous supplies and the increase in manufacturing cost, production in the briquet industry reached an all-time high of 1,748,300 net tons in 1942—a 35-percent increase over 1941, the former record year; the output of packaged fuel (considered separately in this report) amounted to 253,048 net tons—a decrease of 6 percent compared with 1941. The combined output totaled 2,001,348 tons, valued at \$13,806,128.

Statistics on fuel briquets have been collected since 1907, when 11 plants produced a total of 66,524 net tons. Data on packaged fuel have been collected since 1935, and for the 5 years following the industry made a remarkable record of growth, attaining the peak production of 284,513 tons in 1940-more than 11 times that pro-

duced in 1935. In 1941 and 1942 production declined.

As during World War I, the scarcity of competing fuels created a very large demand in 1942 for briquets for domestic use; the trend toward utilization of fireplaces as an added source of heat has brought briquets and packaged fuel into greater service.2 Despite the heavy demand for these fuels, the industries, especially the packaged-fuel industry, have suffered from inability to obtain the raw materials of manufacture, labor, and necessary repair parts, as well as from the increased cost of these items, which forced many plants to discontinue operation for the war, some permanently. No sales of bri-

A STATE OF THE STA

· 大学を変えるというので、本の日の一次のではない

¹ Directories of fuel-briquetting and packaged-fuel plants operating in 1942 will be furnished, on request, by the Coal Economics Division, Bureau of Mines, Washington, D. C. Names of manufacturers of equipment will not be issued for 1942, as companies formerly listed therein did not manufacture fuel-briquetting machinery in 1942 owing to pressure of war work.
Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.
Data on employment and the principal expenses in the manufacture of fuel briquets may be obtained from the Bureau of the Census, which collects and publishes such data in alternate years; 1939 is the latest year for which such data have been collected.

Briquets made from charcoal, wood wastes, and fruit pits are not included in the Bureau of Mines review.

Black Diamond, Chicago and Central Western Market: Vol. 109, No. 11, 1942, p. 46.
Saward's Journal, Boston Market: Vol. 25, No. 36, 1942, p. 430.

quetting or packaged-fuel equipment were reported for 1942 by the manufacturers of such machinery because of priorities, but a number

indicated the diversion of their business to war work.

In an effort to meet urgent fuel needs, various briquetting projects have been advanced in foreign countries. Inquiries from Argentina concerning the possibilities of briquetting surpluses of corn and corn husks have resulted in the construction of a plant for the manufacture of corn briquets for domestic and industrial fuel uses, and American machinery has recently been installed at the Brazeau Collieries, Ltd., in Canada, for producing binderless briquets from coal fines.3

Technologic developments.—The briquetting and packaged-fuel industries continued their research in 1942, although a number of

projects were laid aside in favor of work of a military nature.

A technologic and economic study of the packaged-fuel industry, which began in the fall of 1941 by V. F. Parry of the Fuels and Explosives Service, Bureau of Mines, Golden, Colo., has been completed and it is expected that the results will be published during 1943.4 study has been completed by V. F. Parry and J. B. Goodman 5 of the Bureau of Mines laboratory in Golden, Colo., dealing with the technical phases of the briquetting industry.

Construction of the commercial-scale briquetting press designed by R. J. Piersol <sup>6</sup> at the Illinois State Geological Survey was completed in 1941, but owing to delays in obtaining the necessary equipment because of war priorities the date for final demonstrations on briquetting various Illinois coals scheduled for 1942 has been postponed

further.

Komarek-Greaves & Co.7 of Chicago, Ill., is reported to have developed a roll press for manufacturing fairly strong briquets from lowvolatile coals without a binder, using pressures of 30,000 to 40,000 pounds per square inch. Three of these presses are operating in Canada.

#### FUEL BRIQUETS

Salient statistics of the fuel-briquetting industry from 1938 to 1942 are summarized in the following table. Detailed data for earlier years, beginning with 1907, are to be found in annual issues of Mineral Resources (part II) and Minerals Yearbook, which include Production and value from 1915 to 1942, chapters on briquetting. inclusive, are presented graphically in figure 1.

<sup>&</sup>lt;sup>3</sup> Mining Congress Journal, Experiences in Briquetting Coking Coal: Vol. 28, No. 4, 1942, pp. 45-47.

<sup>4</sup> Parry, V. F., Technical and Economic Study of Packaged Ftlel: Bureau of Mines Rept. of Investigations (in preparation).

<sup>5</sup> Parry, V. F., and Goodman, J. B., Briquetting of Subbituminous Coal: Bureau of Mines Rept. of Investigations 3707.

<sup>6</sup> Piersol, R. J., Briquetting Illinois Coals Without a Binder by Compression and by Impact: Illinois State Geol. Survey Rept. of Investigations 31, 1933, 70 pp.; Briquetting Illinois Coals Without a Binder by Impact: Illinois State Geol. Survey Rept. of Investigations 37, 1935, 75 pp.; Smokeless Briquets; Impacted Without Binder from Partially Volatilized Illinois Coals: Illinois State Geol. Survey Rept. of Investigations 41, 1936, 30 pp.; The Smoke Index: Coal Heat, vol. 39, No. 2, 1941, pp. 59-60; Study Illinois Coals: Coal Heat, vol. 40, No. 3, 1941, p. 16.

<sup>7</sup> Mining and Metallurgy, vol. 24, No. 434, 1943, p. 80.




FIGURE 1.—Production of fuel briquets, number of plants in operation, and average value per ton, f. o. b plant (Central States), 1915-42.

Salient statistics of the fuel-briquetting industry in the United States, 1938-42 [Data regarding packaged fuel are given separately at end of this chapter]

		Produ	ıction			70	Con-	Value of pro-		Aver- age out-		ge value f. o. b. j	per net plant
Year	East- ern States	Cen- tral States	Pacific Coast States		Im- ports	Ex- ports <sup>1</sup>	sump- tion <sup>2</sup>	(thou- sands of dol-	Plants in opera- tion		East- ern States	Cen- tral States	Pacific Coast States
		7	Chousan	ds of n	et tons	B. 1		lars)		tons)			
1938 1939 1940 1941 1942	251 243 331 458 565	546 574 652 752 1,048	74 75 68 89 135	871 892 1, 051 1, 299 1, 748	14 1 (8) (9)	17 13 23 40 104	868 880 1,028 1,259 1,644	5, 702 5, 802 6, 439 8, 002 11, 266	35 31 32 32 32 30	25 29 33 41 58	\$4. 34 4. 23 3. 95 4. 21 4. 56	\$7. 18 7. 15 6. 95 7. 09 7. 04	\$9.38 8.96 8.84 8.36 9.69

<sup>&</sup>lt;sup>1</sup> Exports reported separately by Department of Commerce beginning with 1937.
<sup>2</sup> Production plus imports minus exports.
<sup>2</sup> Less than 1,000 tons.

Production.—The output of fuel briquets in 1942—1,748,300 net tons valued at \$11,266,041—represents an increase of 35 percent in tonnage and 41 percent in value over 1941, the previous record production year. This increase in production in 1942 is readily explained by the general increase in demand for fuels of all kinds in time of war. The present full rated capacity of the industry is nearly double the

1942 production.

Briquets were produced in 14 States, and all but 3 showed increases over 1941. Almost half of the output came from Wisconsin, where production increased 40 percent over 1941; West Virginia, Pennsylvania, and Missouri followed in order, with large increases in production. In Missouri three plants, two of which were new in 1942, produced a total of 104,415 tons valued at \$589,466. Output for the 12 States (other than Wisconsin and Missouri) that produced briquets in 1942 cannot be shown separately without revealing individual data. The large quantities of bituminous slack available at Lake ports, resulting from rehandling of coal at the docks, have helped to make Wisconsin the leading State in production of fuel briquets.

Production of fuel briquets in the United States, 1941-42

		1941				1942		
	Plants	Net tons	Value	Plants	Net tons	Value	Percent crease 1941	over
							Ton- nage	Value
Eastern States	4 23 5	457, 511 751, 801 89, 294	\$1, 926, 048 5, 329, 408 746, 373	3 23 4	565, 675 1, 047, 747 134, 878	\$2, 580, 934 7, 378, 165 1, 306, 942	23. 6 39. 4 51. 0	34. 0 38. 4 75.
	1 32	1, 298, 606	8, 001, 829	1 30	1, 748, 300	11, 266, 041	34. 6	40.

<sup>&</sup>lt;sup>1</sup> 1941: 10 plants in Wisconsin; 2 each in California, Illinois, Michigan, Nebraska, Washington, and West Virginia; and 1 each in Arkansas, Massachusetts, Minnesota, Missouri, North Dakota, Ohio, Oregon, Pennsylvania, Texas, and Wyoming; 1942: 10 plants in Wisconsin; 3 in Missouri, 2 each in California, Illinois, Michigan, Nebraska, and West Virginia; and 1 each in Arkansas, Minnesota, North Dakota, Oregon, Pennsylvania, Washington, and Wyoming.

#### Production of fuel briquets in Wisconsin, 1937-42

Year	Plants	Net tons	Value	Year	Plants	Net tons	Value
1937	10	507, 462	\$3, 639, 183	1940	11	487, 574	\$3, 440, 676
1938	10	422, 281	3, 085, 873	1941	10	535, 457	3, 870, 077
1939	10	430, 554	3, 158, 859	1942	10	750, 417	5, 498, 748

Other large plants are located at coal mines, chiefly in West Virginia and Pennsylvania, and smaller operations at gas plants and petroleum refineries, principally in the Pacific Coast States.

Nearly 51,000 net tons of bulk briquets were packaged at producing plants by 13 operators. No data are available on the quantity of

briquets packaged by retailers.

As briquets are used mostly for domestic space heating, production normally is highly seasonal. However, in 1942 wartime demands resulted in more uniform production than in previous years. Twenty-

<sup>&</sup>lt;sup>8</sup> Black Diamond, Twin Cities and Northwest: Vol. 109, No. 9, 1942, p. 48; Kansas City News Notes: Vol. 109, No. 12, 1942, p. 57.

THE RESERVE OF THE PARTY OF THE

three of the 30 active plants were operated every month of the year, and only 2 less than 6 months—1 of these was a new company that

began operations in October.

In 1942, production was lowest in March, but in May it stepped up markedly. According to the Weather Bureau, below-normal temperatures prevailed during May in the North Central States, where the bulk of briquet consumption is concentrated. The unusual jump in production for October, when above-normal warmth prevailed, can be explained no doubt by the anticipated heavy seasonal demands because of a threatened scarcity of competing fuels.

Monthly production of fuel briquets in the United States, 1940-42, in net tons

Month	1940	1941	1942	Month	1940	1941	1942
January February March April May June July	157, 091 76, 550 68, 981 43, 936 66, 449 57, 814 76, 148	135, 532 118, 596 85, 728 27, 252 82, 723 105, 307 126, 022	170, 991 122, 083 93, 668 102, 514 145, 792 146, 389 134, 145	August September October November December	58, 706 84, 466 92, 295 128, 301 140, 133 1, 050, 870	109, 487 107, 257 120, 197 143, 339 137, 166 1, 298, 606	112, 434 139, 699 204, 665 177, 938 197, 982 1, 748, 300

Value.—Sales realizations on briquets vary considerably in the widely separated producing centers in a given year, therefore an average value per ton for the entire industry has little significance because conditions under which briquets are manufactured and sold differ throughout the country. The most important factors that influence the value per ton realized at any plant are the cost of raw materials, labor, and price of competing fuels; hence, the trend of fuelbriquet prices in the past 5 years is indicated best in this review by considering the average values in the Eastern, Central, and Pacific Coast States separately, as shown in the last three columns of the These figures are the values received by salient statistics table. producers for the total product (exclusive of delivery charges) and not the prices paid by consumers. Some plants are far from the markets they serve, and transportation charges and the margin of the wholesaler or retailer—sometimes both—must be added to the value at the plant.

The total value of fuel briquets manufactured in 1942 was \$11,266,041 f. o. b. plant, an increase of \$3,264,212 (41 percent) over 1941. This large increase is due to a great extent to the 35-percent increase in

production.

In the eastern part of the United States the average value (\$4.56 per ton) was relatively low because all the output came from plants in the low-volatile bituminous fields of West Virginia and in the anthracite region of Pennsylvania, where freight charges are a small proportion of the cost of raw fuel. In the Central States, where the average value was \$7.04 per ton, the major part of the production comes from the docks at Lakes Michigan and Superior, and the cost of raw fuel at these plants involves a considerable freight charge. In the Pacific Coast States, where residual carbon from the manufacture of oil gas constitutes the greater part of the raw fuel used, the average value increased from \$8.36 in 1941 to \$9.69 in 1942.

Baldwin, J. L., The Weather of 1942 in the United States: U. S. Dept. of Commerce Monthly Weather Rev., vol. 70, No. 12, December 1942, pp. 271-273.

Prices.—The following monthly fuel-briquet prices, by cities, for 1941-42 are based upon cash delivery in 1-ton (2,000-pound) lots for retail sales to household consumers at the curb or into the customer's bin (without extra handling or additional charge).

Retail fuel-briquet prices per net ton, 1941-42, by cities and months1

	Janı	ıary	Febr	uary	Ma	rch	Ap	ril	M	ау	Ju	ne
City	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942
Baltimore, Md	\$9.75	\$11.00	\$9. 75	\$11.00	\$9.75	\$11.00	\$9.75	\$11.00		\$11.00	\$9.82	
Boston, Mass		13.75		13.75	12.50	13.75	12.50		12.50	13.75	12, 22	13. 77
Charleston, S. C	13. 33	14.08	13.33	14.08	13.33		13. 33	14.08	13. 33	14.08	13, 33	14.08
Chicago, Ill.2	11.65		11.65	12. 21	11.65	12, 21	11.65	12.04	11.71	12. 26	11.71	12, 26
Cincinnati, Ohio 3	8. 56		8. 56		8.56	9, 21	8, 63	8, 99	8.50	9. 22	8, 50	9. 28
Cincinnati, Onio	8.39		8.39		8.39	9. 63	8. 39	9.39	8.39	9. 39	8, 39	9. 42
Columbus, Ohio 3	12. 50		12. 50		12.50		12, 50		12.50	13. 75	12.50	13.80
Fall River, Mass	12. 50	10.75	9.69		9.69		9, 69		9.69	10.05	9. 56	10.0
Kansas City, Mo. <sup>2</sup> Los Angeles, Calif. <sup>3</sup>	9.69				17. 20		17. 10	19.76	16.89	19.76	16.89	20. 73
Los Angeles, Calif.	17.00		17.00		8.00		8.00	8.75	8.00	8. 75	8. 15	8. 7
Louisville, Ky Manchester, N. H	8.00	8.70	8.00		12,75		12.75		12, 75	14.00		14.00
Manchester, N. H	12.75	14.00	12.75		10.90		10.90		10.89	11.74		11. 7
Milwaukee, Wis	10.90		10.90				12.80		12. 44			13.0
Minneapolis, Minn	12.80		12.80		12.80							11.50
Norfolk, Va	10.50	11.50	10.50	11.50	10.50				11.88			12.1
Norfolk, Va Providence, R. I	11.97	12.13	11.88		11.88				10.00			11.4
Richmond, Va	10.50	11.42	10. 00		10.50				9.95	10.62		10. 7
Richmond, Va St. Louis, Mo. <sup>2</sup> St. Paul, Minn	9.95	10.80	9.95		9.95	10.80				12.96		13.0
St. Paul, Minn	12.80		12.80		12.80	13.05			20 60	21.63		21.6
San Francisco, Calif.	20.00	21.63	20.60		20.60						13.65	(4)
Souttle Wash 3	13.90	14, 36					13. 39	14, 42	13. 52			
Washington, D. C.	11.05	11.62	11.05	11.50	11.05	11.50	11.05	11.53	11.05	11.56	11.00	11.0
	<u> </u>			1			<del> </del>		<u>                                     </u>			
	Jı	ıly	Au	gust	Septe	ember	Oct	ober	Nove	mber	Dece	mber
City		1 1 1 1	7 100	1		Τ		1				1
	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942	1941	1942
					-							-
Baltimore, Md	\$10.50	\$11.02	\$11.00	\$11.02	\$11.00	\$11.02	\$11.00	\$11.02	\$11.00 13.75	\$11.02 13.77	\$11.00 13.75	\$11.0 13.7
Boston, Mass	13. 2	5 13.77	1 13. 20	10. 11	10. 10	10. 11	10. 10	10. 11	10			
Boston, Mass. Charleston, S. C.	13. 33	3 14.08	14.08	14.08								
Chicago III 2	1 11.8	11 12. ZO	11, 96	12. 26	11.96	12. 26						
Cincinnati, Ohio 3	8, 88	9. 28	9.2									
Columbus, Ohio 3	8.70	9.53										
Fall River, Mass	13.00	13.80										6 10.
Kansas City, Mo. <sup>2</sup> Los Angeles, Calif. <sup>3</sup>	10.0	10.05	10.0		10.0				10.0		19.43	
Los Angeles Calif 3	18.00	20. 73			18.6					20. 10	8.70	8.
		5 8.77	8.4						8.70			
Louisville, Ky	1 8.2					14.00	) 14.00	14.00				
Louisville, Ky	13.0	14.00	13. 50									
Louisville, Ky	1 10.8	61 11.78	13. 50 11. 2	7 11. 75	11. 2	7 11.75	11.7	7 11.77				
Louisville, Ky  Manchester, N. H  Milwaukee, Wis  Minneapolis, Minn	10.8	6 11.78 0 13.10	13. 50 11. 2 12. 9	7 11. 75 2 13. 10	11. 2 13. 0	7 11.78 5 13.10	11.7	7 11.77 5 13.10	13.0	5 13. 10	13.05	
Louisville, Ky Manchester, N. H Milwaukee, Wis Minneapolis, Minn Norfolk, Va	10. 8 12. 7 10. 5	6 11.78 0 13.10 0 11.50	13. 50 11. 2 12. 9 11. 0	7 11.75 2 13.10 0 11.50	11. 2 13. 0 11. 0	7 11. 78 5 13. 10 0 11. 50	11. 77 13. 04 11. 50	7 11.77 5 13.10 0 11.50	13.0	13. 10 11. 50	13.05 11.50	11.
Louisville, Ky.  Manchester, N. H.  Milwaukee, Wis.  Minneapolis, Minn  Norfolk, Va.  Providence, R. I.	10. 8 12. 7 10. 5 12. 1	6 11.78 0 13.10 0 11.50 3 12.13	13. 50 11. 2 12. 9 11. 0 11. 0 12. 1	7 11.75 2 13.10 0 11.50 3 12.13	11. 2 13. 0 11. 0 12. 1	7 11.78 5 13.10 0 11.50 3 (4)	11. 77 13. 04 11. 50 12. 13	7 11.77 5 13.10 0 11.50 3 (4)	13. 0. 11. 50 12. 1	13. 10 11. 50 3 (4)	13. 05 11. 50 12. 13	11. (4)
Louisville, Ky.  Manchester, N. H.  Milwaukee, Wis.  Minneapolis, Minn  Norfolk, Va.  Providence, R. I.	10. 8 12. 7 10. 5 12. 1	6 11.78 0 13.10 0 11.50 3 12.13	13. 50 11. 2 12. 9 11. 0 11. 0 12. 1	7 11.75 2 13.10 0 11.50 3 12.13 0 11.42	11. 27 13. 03 11. 00 12. 13 2 11. 17	7 11. 78 5 13. 10 0 11. 50 3 (4) 7 11. 33	11.77 13.00 11.50 12.13 11.17	7 11. 77 5 13. 10 0 11. 50 3 (4) 7 11. 33	13. 04 11. 50 12. 13 11. 17	5 13.10 11.50 3 (4) 7 11.33	13.05 11.50 12.13 11.42	11. 3 (4) 2 11.
Louisville, Ky. Manchester, N. H. Milwaukee, Wis. Minneapolis, Minn Norfolk, Va Providence, R. I. Richmond, Va. St. Louis Mo. <sup>2</sup>	10. 8 12. 7 10. 5 12. 1 10. 5	6 11.76 0 13.10 0 11.50 3 12.13 0 11.42 2 10.76	13. 50 11. 2 12. 9 11. 0 11. 0 12. 1 2 10. 5	7 11. 75 2 13. 10 0 11. 50 3 12. 13 0 11. 42 9 (4)	11. 2 13. 0 11. 0 12. 1 11. 1 10. 4	7 11. 78 5 13. 10 0 11. 50 3 (4) 7 11. 33 7 10. 91	11. 77 13. 04 11. 50 12. 13 11. 17 1 10. 63	7 11.77 5 13.10 0 11.50 3 (4) 7 11.33 2 10.91	13. 05 11. 50 12. 13 11. 17 10. 80	13. 10 11. 50 3 (4) 7 11. 33 10. 87	13.05 11.50 12.13 11.42 10.80	11. (4) 2 11. (2) 10. (3)
Louisville, Ky Manchester, N. H. Milwaukee, Wis. Minneapolis, Minn Norfolk, Va. Providence, R. I. Richmond, Va. St. Louis, Mo. <sup>2</sup>	10. 8 12. 7 10. 5 12. 1 10. 5	6 11.76 0 13.10 0 11.50 3 12.13 0 11.42 2 10.76	13. 50 5 11. 2 12. 9 11. 0 11. 0 12. 1 2 10. 5 5 10. 3	7 11. 75 2 13. 10 0 11. 50 3 12. 13 0 11. 42 9 (4)	11. 2 13. 0 11. 0 12. 1 11. 1 10. 4	7 11. 75 5 13. 10 0 11. 50 3 (4) 7 11. 33 7 10. 91	11. 77 13. 05 11. 50 12. 13 11. 17 10. 65 13. 06	7 11.77 5 13.10 0 11.50 3 (4) 7 11.33 2 10.91 5 13.10	13. 04 11. 50 12. 13 3 11. 17 1 10. 80 1 13. 04	13. 10 11. 50 3 (4) 7 11. 33 0 10. 87 5 13. 10	13. 05 11. 50 12. 13 11. 42 10. 80 13. 05	11. (4) 2 11. (5) 10. (6) 5 13.
Louisville, Ky. Manchester, N. H. Milwaukee, Wis. Minneapolis, Minn Norfolk, Va Providence, R. I. Richmond, Va. St. Louis Mo. <sup>2</sup>	10. 8 12. 7 10. 5 12. 1 10. 5	6 11.76 0 13.10 0 11.50 3 12.13 0 11.42 2 10.76	13. 50 11. 2' 12. 9: 11. 0 11. 0 11. 0 11. 5 10. 5 10. 3 12. 9	7 11. 75 2 13. 10 0 11. 50 3 12. 13 0 11. 42 9 (4) 5 13. 10	11. 27 13. 04 11. 00 12. 13 2 11. 17 10. 47 13. 00	7 11. 78 5 13. 10 0 11. 50 8 (4) 7 11. 38 7 10. 91 5 13. 10	5 11. 77 13. 05 11. 50 12. 13 3 11. 17 1 10. 65 0 13. 05 20. 6	7 11. 77 5 13. 10 0 11. 50 3 (4) 7 11. 33 2 10. 91 5 13. 10 0 (4)	13. 04 11. 50 12. 13 11. 17 10. 80 13. 04 21. 63	13. 10 11. 50 3 (4) 7 11. 33 0 10. 87 5 13. 10	13. 05 11. 50 12. 13 11. 42 7 10. 80 13. 05 21. 63	11. 4 3 (4) 2 11. 3 10. 3 5 13. (4)
Louisville, Ky Manchester, N. H. Milwaukee, Wis Minneapolis, Minn Norfolk, Va. Providence, R. I. Richmond, Va. St. Louis, Mo. <sup>2</sup> St. Paul, Minn San Francisco, Calif. <sup>3</sup> Seattle Wash. <sup>3</sup>	10. 8 12. 7 10. 5 12. 1 10. 5 10. 1 12. 7 20. 6	6 11.76 0 13.10 0 11.50 3 12.13 0 11.42 2 10.76	13. 50 11. 2' 12. 9: 11. 0 11. 0 11. 0 11. 5 10. 5 10. 3 12. 9	7 11.75 2 13.10 0 11.50 3 12.13 0 11.42 9 (4) 5 13.10 0 21.63	11. 27 13. 04 11. 00 12. 13 2 11. 17 10. 47 13. 00	7 11. 78 5 13. 10 7 11. 50 7 11. 33 7 10. 91 5 13. 10 6 (4) 0 (4)	5 11. 77 13. 04 11. 50 12. 13 11. 17 1 10. 65 13. 04 20. 66 14. 25	7 11. 77 5 13. 10 11. 50 (4) 7 11. 33 2 10. 91 5 13. 10 (4) 9 (4)	13. 04 11. 50 12. 13 11. 17 10. 80 21. 60 14. 2	5 13. 10 11. 50 3 (4) 7 11. 33 0 10. 83 5 13. 10 8 (4) 9 (4)	13.05 11.50 12.13 11.42 10.80 13.05 21.63 14.29	11. 8 (4) 2 11. 3 10. 8 5 13. (4) 9 (4)
Louisville, Ky.  Manchester, N. H.  Milwaukee, Wis.  Minneapolis, Minn  Norfolk, Va.  Providence. R. I.	10. 8 12. 7 10. 5 12. 1 10. 5 10. 1 12. 7 20. 6	6 11. 75 0 13. 10 0 11. 50 3 12. 13 0 11. 42 2 10. 76 0 13. 10 0 21. 63 8 (4)	13. 50 11. 2' 12. 9: 11. 0 11. 0 11. 0 11. 0 11. 0 11. 0 11. 0 12. 1 10. 5 10. 3 12. 9 12. 9 10. 5 10. 3 12. 9 12. 9 10. 5 10. 3 10. 6 10. 6	7 11.75 2 13.10 0 11.50 3 12.13 0 11.42 9 (4) 5 13.10 0 21.63 0 (4)	11. 2 13. 0 11. 0 12. 1 11. 1 10. 4 13. 0 13. 0 13. 0 13. 9	7 11. 78 5 13. 10 0 11. 50 3 (4) 7 11. 33 7 10. 91 5 13. 10 0 (4) 0 (4)	5 11. 77 13. 04 11. 50 12. 13 11. 17 1 10. 65 13. 04 20. 66 14. 25	7 11. 77 5 13. 10 11. 50 (4) 11. 33 2 10. 91 5 13. 10 (4) 9 (4)	13. 04 11. 50 12. 13 11. 17 10. 80 21. 60 14. 2	5 13. 10 11. 50 3 (4) 7 11. 33 10. 83 5 13. 10 8 (4) 9 (4)	13.05 11.50 12.13 11.42 10.80 13.05 21.63 14.29	11. 8 (4) 2 11. 3 10. 8 5 13. (4) 9 (4)

Compiled from reports of Retail Price Division, Bureau of Labor St

Number of plants.—Records show 30 plants in commercial operation in 1942; all but 2 of these (the new briquetting plant of the Smokeless Coal Blox Co. 10 and that of the St. Louis Briquette Co., Inc., both at St. Louis) were also active in 1941. One plant active in 1941 failed to report operations for 1942. Nine plants were idle in 1942; of these, 6 were also idle in 1941, and 3 went out of business. Of the 2 reported as under construction in 1941 to begin operations in 1942, 1-

Includes 2-percent sales tax. Includes 3-percent sales tax.

Data not available.
Price per ton of 2,240 pounds.
Not comparable with preceding months.

<sup>10</sup> Black Diamond. St. Louis News Notes: Vol. 107, No. 11, 1941, p. 43.

the Smokeless Coal Blox Co., at St. Louis—went into commercial production in 1942. In 1942 the Binkley Coal Co. purchased the Standard Briquet Fuel Co. plant at Kansas City, which it had been operating as lessee since 1935.

Size of plants.—The following table classifies the plants operating in 1941 and 1942 according to actual production as well as rated capacity. Rated capacity, of course, is the better indicator of the

relative size of plants.

The total annual rated capacity of the 30 plants active in 1942, as shown on operators' reports, was over 3 million net tons. It should be noted that, notwithstanding the great increase in production over 1941, these 30 plants could nearly double their 1942 output should demand warrant.

The average output of individual plants increased from 41,000 tons in 1941 to 58,000 in 1942 (41 percent). Twenty-three plants operated every month and produced 1,709,997 tons or about 98 percent of the total.

Classification of briquetting plants in the United States, 1941-42, by size of output and annual capacity

Output (net tons)	Pl	ants	Annual conscitu (not tons)	Plan	ats
Less than 2,000 2,000 and less than 5,000 10,000 and less than 25,000 25,000 and less than 25,000 25,000 and less than 100,000 100,000 and less than 100,000	1941 6 2 3 9 6 6	1942 2 3 5 5 9 6	Annual capacity (net tons)  Less than 5,000. 5,000 and less than 10,000. 10,000 and less than 25,000 25,000 and less than 100,000. 100,000 and less than 200,000. 200,000 and less than 400,000. 400,000 and over.	1941 2 4 6 11 5 2 2	1942 1 2 7 9 7 2 2
	32	30		32	30

Raw fuels.—The number of plants, classified according to type of fuel used in 1942, was as follows:

Classification of fuel-briquetting plants in the United States in 1942, by kinds of raw

fuel used	
Kind of raw fuel used:	Plants
Anthracite and semianthracite fines exclusively	6
Mixture of Pennsylvania anthracite and bituminous_	 4
Bituminous:	
Low-volatile	14
High-volatile	77
Semicoke (lignite char)	 ĩ
Residual carbon from nurolysis of natural gas	i
Residual carbon from manufacture of oil gas	 5
Petroleum coke	 6
	 4 0 0

 $^14$  plants made 2 kinds and 2 plants 3 kinds of briquets; hence, the sum of the items exceeds the total number of plants.

It is noteworthy that in 1942 the production of fuel briquets from petroleum coke, which in recent years had been used in increased amounts, dropped far below the 1941 figure. Large quantities of petroleum coke are now used for manufacturing ashless carbon electrodes essential in producing aluminum and other metals by electrometallurgical processes.

A small tonnage of raw Texas lignite was made into briquets in 1940

and 1941, but no briquets were produced from such raw material in 1942, owing to the labor shortage and the general effect of the war on small industries. In 1942 six operations reported making more than one kind of briquet—four plants made two kinds and two plants made three kinds. Six operators reported washing a total of 349,100 tons of raw fuel before using it in the manufacture of briquets.

Raw fuels used in making fuel briquets in the United States, 1941-42

	Net	tons	Percent	of tota
Raw fuel	1941	1942	1941	1942
Anthracite and semianthracite culm and fine sizes	265, 637 1 787, 722	386, 947 1, 077, 474	21. 6 64. 1	23. 4 65. 3
Residual carbons from oil-gas manufacture and natural-gas pyrolysis; petroleum coke; and semicoke (lignite char)	175, 043	187, 207	14. 3	11. 3
	1, 228, 402	1, 651, 628	100.0	100. 0

<sup>1</sup> Includes small tonnage of Texas lignite used without charring.

Production of fuel briquets, 1941-42, grouped according to location of plants with reference to supply of raw fuel

	Net to	ons	Percent
Location of plant	1941	1942	of change in 1942
At or near Lake Superior or Lake Michigan coal docks	560, 506 579, 844 142, 378 15, 878	782, 436 789, 535 163, 294 13, 035	+39. 6 +36. 2 +14. 7 -17. 9
	1, 298, 606	1, 748, 300	+34.6

<sup>1</sup> Jackson, Mich., and Omaha, Nebr.

Binders.—The following table classifies the fuel-briquet plants by type and percentage of binder used. As indicated in the table, asphaltic pitch continues to be the preferred binder in briquetting coal and coke. Approximately 102,000 tons of asphaltic pitch and smaller amounts of other binders were used in 1942 in the manufacture of fuel briquets.

In 1942, as in 1941, three plants used no binder; two of these briquetted the carbon residue from the manufacture of oil gas, and one

used low-volatile bituminous coal.

Classification of briquetting plants in the United States in 1942, by type and percentage of binder used

		Produc	tion			Produc	tion
Type of binder	Plants	Net tons	Percent of total	Ratio of binder to raw fuel (by weight)	Plants	Net tons	Per- cent of total
Asphaltic pitch Mixed pitches	22 1 2 2 2 1 3	1, 390, 481 239, 092 118, 727	79. 5 13. 7 6. 8	Less than 5 percent. 5 and less than 7 percent. 7 and less than 9 percent. 9 percent and over. No binder.	4 12 9 2 13	197, 236 548, 834 } 883, 503 118, 727	11. 3 31. 4 50. 5 6. 8
	30	1,748,300	100.0		30	1,748,300	100.0

<sup>&</sup>lt;sup>1</sup> 2 plants use residual carbon from manufacture of oil gas and 1 uses bituminous coal as raw fuel.

Weight and shape.—Pillow-shaped briquets continue to be the most popular in the United States. Of the 30 active plants in 1942, 24 produced 1,250,360 tons (72 percent) of this type briquet, 4 plants 19,034 tons (about 1 percent) of cube-shaped briquets, and 3 plants 478,906 tons (27 percent) of the cylindrical type. One of these made both pillow- and cube-shaped briquets; hence, the sum of the plants described above exceeds by 1 the total number of active plants. Records show two plants making briquets in 1942 in more than one shape and three plants making two sizes.

Prevailing weight of briquets produced in the United States in 1942

		Produc	tion			Produc	tion
Weight (ounces)	Plants	Net tons	Per- cent of total	Weight (ounces)	Plants	Net tons	Per- cent of total
Less than 2	3 11 7 5	45, 757 926, 975 536, 565 162, 572	2. 6 53. 0 30. 7 9. 3	6 and under 10 10 and under 16 16 and under 25	1 4	} 76, 431 1, 748, 300	4.4

<sup>&</sup>lt;sup>1</sup>1 plant made a 2-ounce pillow briquet and a 24-ounce cube; hence, the sum of these items exceeds the total number of plants.

Distribution.—According to reports received, shipments of briquets during 1942 increased 27 percent over 1941; they were shipped into 37 States and the District of Columbia and exported to other countries.<sup>11</sup>

It is not possible to show shipments from each producing State because there are only one or two producers in each of the States except Missouri and Wisconsin, and confidential reports of individual companies would thus be revealed. However, for a graphic presentation of the centers of production for 1928 and 1936, with corresponding States of destination, see Minerals Yearbook, 1937 (p. 965, fig. 65).

Generally, rail shipments represent consumption at distant points, and shipments by truck show local and nearby consumption.

Shipments of fuel briquets of domestic manufacture, 1941-42, by States of destination, as reported by producers, in net tons

State	1941	1942	State	1941	1942
Alaska	2, 213 256	376	New Hampshire New Jersey	3, 210 871	2, 551 1, 139
Arkansas	14,075	17, 798	New York	25, 141	26, 097
Connecticut	844	1, 544	North Carolina		12, 894
Delaware	208	516	North Dakota	80, 136	96, 912
District of Columbia	248	520	Ohio		54, 699
Florida	591	503	Oklahoma.	43	61
Georgia	238	178	Oregon		77, 204
Illinois	50, 398	65, 709	Pennsylvania		21, 999
Indiana	45, 934	48, 868	Rhode Island	3, 843	4, 070
Iowa	31, 608	47, 392	South Carolina	4, 798	4, 890
Kansas	4, 957	10, 731	South Dakota	64, 026	73, 744
Kentucky	5, 734	4,954	Texas	178	
Louisiana	48		Vermont	238	195
Maine	4, 828	6, 254	Virginia	18, 187	17, 370
Maryland	2, 969	3, 765	Washington	42, 977	21, 505
Massachusetts	38, 756	38, 978	West Virginia	339	322
Michigan	107, 217	107, 576	Wisconsin	220, 939	317, 627
Minnesota	244, 767	303, 497	Wyoming	1, 576	409
Missouri	82, 954	172, 269			
Montana	22	73		1, 256, 964	1, 600, 300
Nebraska	23, 992	35, 111			

<sup>11</sup> See also followin table of exports

Direct shipments of fuel briquets by rail and truck, 1941-42, as reported by producers, in net tons 1

		1941			1942	
Produced in—	Rail	Truck <sup>2</sup>	Total	Rail	Truck 2	Total
Eastern States Central States Pacific Coast States	447, 458 569, 295 38, 377	8,428 181,849 54,184	455, 886 751, 144 92, 561	550, 220 829, 858 27, 746	16, 244 212, 584 88, 434	566, 464 1, 042, 442 116, 180
Total United States	1, 055, 130	244, 461	1, 299, 591	1, 407, 824	317, 262	1, 725, 086

Includes shipments outside the United States.
Includes local deliveries.

Imports and exports.—Before 1922 the quantity of fuel briquets imported into the United States was negligible. The anthracite shortages of 1922-23 and 1925-26, however, created a demand for the European product (mostly from Germany, Belgium, and France, and mainly for consumption in the anthracite-consuming States), which in 1926 reached a peak of 123,593 net tons. Imports continued at a comparatively high level through 1932, when they totaled 80,288 tons. Thereafter they dropped sharply and since September 1939—the beginning of the war-have virtually ceased. In 1941, 162 tons were imported from Canada; and in 1942, 325 tons came from Canada and 9 tons from the United Kingdom.

Figures for imports of briquets since 1919 (the first year of record) are included in annual volumes of Mineral Resources and Minerals Yearbook. 12

Briquets (coal and coke) and other composition coals for fuels imported for consumption in the United States, 1938-42

	110				
Year	Net tons	Value	Year	Net tons	Value
1938	13, 814	\$67, 366	1941	162	\$791
1939	1, 344	5, 752	1942	334	1, 739
1940					Salat Salat

Wartime fuel demands are reflected in briquet-export data. dian shipments in 1942 amounted to 103,329 net tons, more than three Canada received 77 percent of the total times the 1941 tonnage. exports in 1941 and 99.5 percent in 1942.

Briquets (coal and coke) exported from the United States, 1941-42, by countries and customs districts

	19	1941 1942			19	)41	19	42	
	Net	Value	Net tons	Value		Net tons	Value	Net tons	Value
Country Brazil	39 29 2 9, 144 1 13 39	12 117 735 288, 593	103, 329 279  12  103, 879	764, 573 3, 068 	Dakota. Duluth and Superior El Paso	155 165 87 9,019 37 1,148 15 166 	1, 172 525 60, 012 308 8, 612 129 2, 232 	1, 709 7 	300, 597 3, 198 9, 648 2, 616 264, 877 117 90
Buffalo	15, 186			132, 205		40, 477	288, 593	103, 879	770, 556

<sup>13 1919-29,</sup> Mineral Resources, 1929, part II, p. 32; 1930-35, Minerals Yearbook, 1936, p. 657.

The second second second

World production.—Official data on production of fuel briquets in other countries since 1939 have been meager, owing to the war.

World production of fuel briquets, 1937-42, by countries, in metric tons 1

[Compiled by	

Country 1	1937	1938	1939	1940	1941	1942
Algoria	68, 682	(2)	(2)	(2)	(2)	(2)
AlgeriaAustralia: Victoria 3	396, 760	420, 704	421, 254	72	(2)	(2)
Belgium		1, 712, 280	1, 561, 210	(2) (2) (2)	(2) (2) (2) (2) (2)	(2)
Dalgonio	47, 106	85, 770	88, 496	100,000	(2)	25
Czechoslovakia:	41, 100	80,110	00, 100	100,000		` '
Czechoslovakia.	459, 680	(2)	(2)	(2)	(2)	(2)
Coal		(2) (2)	\ <u>\</u>	(2) (2)	(2) (2) 15, 446	(2) (2)
Lignite Eire (Irish Free State)	264, 482	20, 501	(2)	5, 337	15 448	(2)
Eire (Irish Free State)	10, 725	20,001	(2) (2) (2) (2)	(2)	(2)	(2)
France	8, 321, 000	7, 475, 000	(4)	(*)	(9)	(-)
Germany: Coal		0.000.015	(0)	. (0)	(9)	(9)
Coal	6, 785, 537	6, 897, 245	(2)	(2) (2) (2)	(2) (2)	(2) (2) (2) (2) (2)
Lignite	41, 951, 141	44,007,268	(2) (2)	(2)	1 52	1 12
Hungary	373, 519	441, 081		(2)	1 52	
Indochina	132, 225	131, 558	185, 400	114,000	(2) (2) (2)	1 12
Hungary Indochina Italy	58, 860	51, 047	(2)	(2)	(2)	(2)
Netherlands:						(0)
Coal	1, 277, 305	1, 262, 716	1, 268, 926	(2) (2)	(2)	(2)
Netherlands: Coal Lignite	49, 539	60, 543	68, 607	(2)	(2)	(2)
Netherlands Indies	55, 349	82, 123	85, 079	99, 315	(2) 20, 220	(3)
Netherlands Indies New Zealand Poland	31, 582	29, 947	29, 889	28, 529	20, 220	(2) (2) (2)
Poland	209, 347	222, 531	(2)	(2)	(2) (2)	(2)
Portugal	7, 772	19,865	(2)	(2)	(2)	(2)
Portugal	262, 330	232, 662	(2)	(2)	(2)	(2)
Spain	342,000	568,000	765, 000	785, 000	4 178,000	(2)
Tunisia Turkey	82, 805	86, 478	(2)	(2)	(2)	(9)
Turkev	14, 761	37, 285	14, 792	24, 497	28, 392	(2)
United Kingdom	826, 600	507, 415	(2)	(2)	(2)	(2)
United States 5	1, 035, 970	936, 402	1,004,902	1, 211, 433	1, 422, 866	1, 815, 583
Yugoslavia	61, 323	100, 945	132, 466	(3)	(2)	(2)
Total 6	64, 975, 680	65, 389, 366	(2)	(2)	(3)	(2)

<sup>&</sup>lt;sup>1</sup> In addition to countries listed, briquets are produced in Canada and New Caledonia, but data on output are not available.

<sup>2</sup> Data not available.

#### PACKAGED FUEL

Packaged fuel differs from fuel briquets in that the former is made up of more or less friable rectangular blocks wrapped together to form neat, tightly fitted packages, which withstand weathering fairly well, eliminate much of the breakage, and provide a relatively clean fuel to They are designed primarily for local or nearby consumption. The packages, wrapped in heavy paper and sealed with gummed tape, usually consist of 3- to 4-inch cubes (six or eight to a package, the package weighing 10 to 15 pounds). Packaged fuel is made from various types of coal or coke screenings, usually mixed with a neutral Its growth in popularity has been due largely to its convenience and cleanliness in handling and to the fact that it may be purchased in less-than-ton lots.

Production of packaged fuel declined in 1942. The phenomenal growth of this industry from 1935 through 1940 is illustrated strikingly in figure 2. In 1941, however, production dropped 5 percent from 1940; and in 1942, it dropped 6 percent from 1941. World War II and competition within the industry are the major factors for the

decline since 1940. The effect of the war on this industry has been felt mostly through increased cost of raw fuels, manufacturing materials, and labor as

Data not available.
 Data for year ended March 31 of year stated.
 January to June, inclusive.
 Includes packaged fuel as follows—1937: 132,482 tons; 1938: 146,012 tons; 1939: 195,504 tons; 1940: 258,105 tons; 1941: 229,560 tons.
 Totals incomplete; they represent sum of figures given in table only.

well as the inability to obtain the same. According to operators' reports, the cost of production in 1942 increased to such an extent that it has made the price of packaged fuel prohibitive and has forced a large number of plants to discontinue operations for the war, some

permanently.

Machinery manufacturers reported no sales for fuel-briquetting or packaged-fuel installations in 1942, principally because of priorities on the necessary materials; a number of them have followed the war trend and diverted their businesses to war work—one manufactured special machinery for briquetting iron ore and flue dust <sup>13</sup> and another a press to be used in research work on the briquetting of

sponge iron.

Processes.—United States operators in 1942 reported no new processes or types of machinery for use in the packaged-fuel industry. The Eberling process <sup>14</sup> was used by 75 manufacturers in 1942. Other processes used were the Glenn-Smith <sup>15</sup> and Leemon <sup>16</sup>; and one manufacturer—the Johnson Coal Cubing Co., <sup>17</sup> of Detroit, Mich., largest operator since 1932—uses a process and equipment of its own design. The process and machine developed in 1939 by the Viking Manufacturing Co., of Jackson, Mich., are not yet in use in the United States, but plans are under way for a number of such installations after the war. These processes are discussed in earlier reports of this series and in the trade journals,

Salient statistics of the packaged-fuel industry from 1937 to 1942 are summarized in the following table; 1935 was the first year for which

such data were collected by the Bureau of Mines.

Salient statistics of the packaged-fuel industry in the United States, 1937-42
[Data regarding fuel briquets are given separately at beginning of this chapter]

	Produc	Production (thousands of net tons)			Diocetata	Average value net ton, f. o. plant		
Year	Eastern and Pacific Coast States	Central States	Total	produc- tion (thou- sands of dollars)	Plants in operation (thou sand of ne	(thou- sands of net tons)	Eastern and Pacific Coast States	Central States \$8.76 8.66 8.62
1937 1938 1939 1940 1941 1942	10 9 9 8 10 8	136 152 207 277 260 245	146 161 216 285 270 253	1, 287 1, 405 1,867 2, 392 2, 472 2, 540	64 76 103 106 103 89	2 2 2 3 3 3	\$9. 62 9. 92 9. 69 10. 12 10. 95 10. 74	8.66

Production and value.—The 89 active plants in 1942 produced 253,048 net tons with a value of \$2,540,087 (see fig. 2); all but 7 of these plants are in the Central States. Production decreased 6 percent from 1941, but the total value increased 3 percent.

Output declined in 8 of the 13 States producing packaged fuel; of the three largest producing States—Michigan, Ohio, and Wisconsin, in order named—only one (Wisconsin) showed an increase in production over 1941.

<sup>13</sup> Steel, Briquetting Machine—Supplies Charge and Feed Ore in Cubes: Vol. 112, No. 2, January 11,

<sup>1943,</sup> pp. 82-84.

18 Eberling, C. M., Packaged Fuel by the Eberling Process: 1938 Catalog, 6002 Ellen Ave., Cleveland, Ohio.

Ohio.

Black Diamond, Briquetting Plant Solves Slack Problem: Vol. 98, No. 6, March 13, 1937, p. 60.

Black Diamond, vol. 102, No. 12, June 17, 1939, p. 15.

Black Diamond, A Mammoth Package Fuel Plant: Vol. 102, No. 7, April 8, 1939, p. 23.

ではないない。 大田のでは、衛子のないのは、人間のは、大田ののはないない。




FIGURE 2.—Production of packaged fuel, number of plants in operation, output per plant, and average value per ton, f. o. b. plant (Central States), 1935-42.

Production of packaged fuel in the United States, 1941-42, by States [Plants and production not included in preceding fuel-briquet tables]

		1941			1942	
	Plants	Net tons	Value	Plants	Net tons	Value
Central States: Illinois. Indiana Iowa. Michigan Minesota. Missouri Nebraska Ohlo Wisconsin Undistributed 3	6 6 2 38 6 4 1 20 13	8, 924 13, 976 (1) 93, 213 28, 377 24, 356 (1) 46, 566 37, 747 7, 136	\$95, 431 126, 560 (1) 796, 226 307, 134 199, 379 (1) 429, 744 345, 239 67, 250	6 5 2 30 4 3 1 22 9	4, 980 16, 698 (1) 89, 080 26, 887 14, 088 (1) 45, 228 41, 203 7, 301	\$60, 001 168, 882 (1) 867, 671 307, 887 119, 578 (1) 456, 896 398, 263 79, 500
Total Central States Eastern and Pacific Coast States	96 3 7	260, 295 9, 549	2, 366, 963 104, 604	82 3 7	245, 465 7, 583	2, 458, 678 81, 409
Total United States	103	269, 844	2, 471, 567	89	253, 048	2, 540, 087

Included under "Undistributed"; Bureau of Mines not at liberty to publish figures.
 Includes States entered as "!" above.
 Maine 2, Pennsylvania 1, Virginia 3, and Washington 1.

The values, by States, in the following table represent the average per ton received by operators in 1941 and 1942 and indicate increases in average realization in each of the eight States shown; similar advances were prevalent in all but one of the other producing States, but these cannot be shown because there were less than three operators

in each State. The values do not represent the price per ton to the consumer, as many plants sell both to retailers and consumers, but rather the average per ton received by producers on the total product (exclusive of delivery charges). The value at the plant comprises cost of coal at the mine, freight rate, direct and indirect manufacturing costs, and profit.

Average value received per net ton of packaged fuel, 1941-42

State	1941	1942	State	1941	1942
Illinois	\$10.69	\$12.05	Missouri	\$8. 19	\$8. 49
Indiana	9.06	10.11	Ohio	9. 23	10. 10
Michigan	8.54	9.74	Virginia	9. 70	10. 06
Minnesota	10.82	11.45	Wisconsin	9. 15	9. 67

Only about one-fifth of the plants in preceding years were active throughout the year, but 42 of the 89 plants active in 1942 operated each month of the year, and only 9 plants operated less than 6 months.

Monthly production of packaged fuel in the United States, 1941-42, in net tons

Month	1941	1942	Month	1941	1942
January February March April May June July	39, 594 37, 727 40, 893 17, 592 6, 318 5, 028 7, 101	33, 924 29, 360 26, 779 19, 353 14, 068 9, 533 7, 68	AugustSeptemberOctoberNovemberDecember	10, 184 17, 422 27, 183 30, 506 30, 296 269, 844	9, 346 18, 519 30, 378 26, 361 27, 739 253, 048

Number of plants.—Eighty-nine plants reported commercial production of packaged fuel in 1942; 85 of these were also active in 1941. There were four new plants in 1942; three of these reported production. One plant in Indiana, new in 1941, started operating in 1942. Eight plants went out of business in 1942; five of these had been in operation part of the year, and three were plants that had been in operation each year for 8 years or more. From 1935 to 1940—the peak year—many plants established themselves firmly and built up a stable business; but during this development period a relatively large number of plants went out of business soon after they began to operate.

Activity in number of packaged-fuel plants, 1937-42

Year	Active	New	Idle	Out of business	Year	Active	New	Idle	Out of business
1937	64	17	6	3	1940	106	16	15	14
1938	76	16	8	1	1941	103	7	8	14
1939	103	29	11	9	1942	89	14	2 16	3 8

Size of plants.—The average annual production per plant increased from 2,600 tons in 1941 to 2,800 in 1942. According to operators' reports the industry, if operated at full capacity, could produce 2½ times its 1942 output.

<sup>1 2</sup> in Michigan and 2 in Ohio; all but 1 active in 1942.
28 in Michigan, 3 in Ohio, 2 in Wisconsin, and 1 each in Idaho, Minnesota, and Missouri; 5 of these also idle in 1941.

<sup>34</sup> in Michigan, 2 in Ohio, and 1 each in Missouri and Idaho; 7 of these active in 1941.

いているを終りのです。

Classification of packaged-fuel plants in the United States, 1941-42, by size of output and annual capacity

Output (net tons)	Pla	nts		Plants		
Output (net tons)	1941	1942	Annual capacity (net tons)	1941	1942	
Less than 500	1 25 19 39 5 9	<sup>2</sup> 20 14 38 6 7	Less than 5,000	68 17 6 6 5	52 21 5 6 4	
25,000 and over	ĭ	1	60,000 and over	1	i	
	103	89		103	89	

<sup>12</sup> of these began operations in the fall of 1941.

Raw fuels.—The kinds and quantities of raw fuels used are shown in the following table. The decrease in petroleum coke (which rose significantly from 1939 to 1941) is due to the War Production Board freeze order on this fuel, which became effective in October 1942.<sup>18</sup>

Low-volatile bituminous cubes were made at 77 plants in 1942, petroleum-coke cubes at 10, high-volatile bituminous cubes at 3, and semianthracite cubes at 2; cubes of mixtures of the various raw fuels were made at 2 plants. Five operators made more than one kind, and three made cubes in two sizes. About 188,000 tons (75 percent) of the total raw fuels were shipped-in slack from the mines and Lake docks; the remainder represents yard screenings. Proportionately fewer operators used shipped-in slack exclusively in 1942 than in 1941—owing to difficulties in obtaining the raw fuels.

Raw fuels used in making packaged fuel in the United States, 1941-42

Raw fuel	Net	tons	Percent	of total
Raw Iuei	1941	1942	1941	1942
Bituminous (high-volatile) and semianthracite	4, 784 213, 474 1 48, 560	8, 053 210, 761 31, 571	1.8 80.0 18.2	3. 2 84. 2 12. 6
	266, 818	250, 385	100.0	100.0

<sup>1</sup> Includes small tonnage of coke breeze.


Binders.—Cornstarches of various types, averaging about 15 pounds per ton of packaged fuel produced, continue to be the principal binders used in the manufacture of packaged fuel. Cement and asphalt—either alone or in combination with starch—were also employed. About 1,600 tons each of starch and asphalt and 83 tons of cement were used by packaged-fuel operators in 1942. The following table classifies the packaged-fuel plants in 1941 and 1942 according to type and percentage of binder used.

Classification of packaged-fuel plants in the United States, 1941-42, by type and percentage of binder used

			,		
Type of binder	Pl	ants	Ratio of binder to raw fuel (by	Plants	
Type of bilider	1941	1942	weight)	1941	1942
Starch Starch and cement Starch and asphalt Cement Asphalt Sulfite cellulose	91 3 1 5 2 1	82 2 1 2 2	Less than 0.5 percent 0.5 and less than 1 percent 1 and less than 2 percent 2 and less than 3 percent 3 and less than 5 percent 5 percent and over	71 26 4	65 19 1 2 2
	103	89	l	103	89

<sup>&</sup>lt;sup>18</sup> Coal Dealer, War Production Board Freezes Stocks of Petroleum Coke: Vol. 39, No. 7. November 1942, p. 23.

<sup>2 1</sup> of these began operations in the fall of 1942.



#### PEAT

By Joseph A. Corgan

#### SUMMARY OUTLINE

	Page		Page
Q	1021	Uses	1023
D	1091	I Imports	1020
Production	1021	World production	1024

#### SUMMARY

Reports received by the Bureau of Mines from producers indicate that the output of peat in the United States in 1942 totaled 71,500 short tons valued at \$516,887—substantially less than in 1941, when the production was 86,503 tons valued at \$657,556. The decline can be attributed largely to cessation or curtailment of operations at many peat bogs because of a shortage of labor. In 1942 imports amounted to 49,236 short tons valued at \$1,219,473, an increase over 1941 of 62 percent in quantity and 73 percent in value. Although the quantity imported in 1942 was considerably below the pre-war figure of 78,611 tons in 1939, the reported value of \$1,219,473 in 1942 was slightly higher than that in 1939 No exports were reported for 1942; thus, the total quantity available for domestic consumption (domestic production plus imports) was 120,736 tons, a gain of 3,891 tons over 1941 but a decline of 13,358 tons from 1939. In the United States, peat is used primarily for soil improvement and in mixed ferti-As in many years past, producers reporting for 1942 showed no use of peat as fuel.

Every effort has been made to cover in the canvass all commercial operations. A directory, listing names and addresses of operators who reported production in 1942 to the Bureau of Mines, has been prepared; it will be sent, upon request, to those who may be interested.

Reserves.—The peat reserves of the United States are extensive and constitute an important item in the natural resources of the country. About half of the States contain some peat reserves. The total, calculated as air-dried peat, has been estimated to be 13,827,000,000 tons. Three of the Great Lakes States—Minnesota, Wisconsin, and Michigan—together contain 75 percent of the reserves, and 14 percent of the country's total is in Florida; in the Pacific Coast region, California contains most of the known deposits.

#### PRODUCTION

Commercial production of peat in the United States was reported to the Bureau of Mines by 41 producers operating in 17 States in 1942, compared with 49 producers in 17 States in 1941. The decline in output from 86,503 short tons in 1941 to 71,500 tons in 1942 and the decrease of 8 in number of producers were caused primarily by the

<sup>&</sup>lt;sup>1</sup> Soper, E. K., and Osbon, C. C., The Occurrence and Uses of Peat in the United States: Geol. Survey Bull. 728, 1922, p. 92.

closing of some plants for the duration of the war and a shortage of labor at others. Some of the operators indicated that former employees are in the armed forces and that the plants will not reopen until the war is over.

The average value of peat per ton was \$7.23 in 1942, compared with \$7.60 in 1941. Production and value for the years 1937 to 1942 are shown in the following table.

Peat produced in the United States, 1937-42

Year	Short tons	Value	Year	Short tons	Value
1937	51, 223	\$305, 156	1940	70, 097	\$516, 865
	45, 933	286, 127	1941	86, 503	657, 556
	55, 483	362, 066	1942	71, 500	516, 887

Figure 1 illustrates graphically the trend in production and value of peat from 1908 to 1926 and 1934 to 1942. The Federal Government made no canvass of the industry from 1927 to 1933, inclusive, and no data for these years are available.




FIGURE 1.—Quantity and value of peat production, 1908-42; no data available for 1927-33.

In 1942 the producing States, in order of output, were: Illinois, New York, Michigan, New Jersey, Iowa, Maine, Pennsylvania, California, Minnesota, Florida, Wisconsin, Connecticut, Ohio, Georgia, Massachusetts, Washington, and New Hampshire. In 1941 New York led in output and was followed by Illinois, New Jersey, and Michigan; the order of the other States also varied from that in 1942.

Peat humus comprised 53 percent of the total production in 1942; reed or sedge peat, 31 percent; and moss peat and other, 16 percent. Peat humus was produced in 9 States, reed or sedge peat in 8, and moss peat in 7.

One plant reported production of kiln-dried peat; 12, raw peat; 14, shredded peat; and 8, cultivated peat.

このできる 大きのでは、大きのでは、大きのできるとのできるというというできる

一日本代の大学の大学の大学の教育を一下には、これでいるという

#### USES

Peat is used for soil improvement on lawns, golf courses, and gardens, and at greenhouses and nurseries; as packing material for plants, shrubs, eggs, fruits, vegetables, and fragile articles; for insulating material; and as litter for livestock and poultry. The principal use of peat in the United States is in agriculture and horticulture as a soil conditioner and an ingredient of fertilizer. In 1942, of the total peat sales 61 percent was used for soil improvement, 30 percent in mixed fertilizers, and 9 percent for other purposes. No sales of peat for fuel in 1942 were reported, although in some European countries it is used extensively for this purpose; reports indicate that efforts are being made to extend its use in countries where supplies of fuels customarily used are deficient.

#### **IMPORTS**

In 1939, before the war became world-wide, peat moss imported for consumption in the United States totaled 78,611 short tons valued at \$1,204,883. In 1942 the quantity imported was 49,236 tons, but the reported value of \$1,219,473 was slightly greater than the value of 1939 imports. Imports were received from 15 countries in 1939, and in that year, as in many earlier years, Germany was the chief source of supply. Netherlands and Sweden also exported large quantities of peat moss to the United States. In 1942 all imports came from Canada and the United Kingdom, the former supplying 49,100 tons and the latter only 136 tons. In 1939 imports from Canada were only 6,922 tons and those from the United Kingdom 785 tons. It is evident from these figures that Canada, now supplying much of the peat moss imported, has replaced Germany, Sweden, Netherlands, and other European countries as the source of imported peat.

Peat moss imported for consumption in the United States, 1937-42

Year	Short tons	Value	Year	Short tons	Value
1937	86, 871	\$1, 219, 127	1940	21, 689	\$454, 632
1938	69, 509	1, 092, 942	1941	30, 342	704, 264
1939	78, 611	1, 204, 883	1942	49, 236	1, 219, 473

With the drastic reduction of imports subsequent to 1939, peat producers in the United States were presented with an excellent opportunity to expand their markets and increase production; however, the closing of some plants because of labor shortages and curtailment of activities at others for the same reason prevented operators from taking full advantage of the situation in 1942.

The pre-war values of the imported product are considerably lower than those of 1942. The average value per ton was \$15.33 in 1939, compared with \$24.77 a ton for 1942. This increase is attributable

almost entirely to the high value of the Canadian product.

Peat moss imported for consumption in the United States, 1941-42, by countries

	P	oultry and	stable gra	de	Fertilizer grade			
Country	1941		1942		1941		1942	
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
Canada Germany	12, 145 16	\$308, 416 388	36, 164	\$943, 385	17, 053	\$374, 143	12, 936	\$273, 576
United Kingdom 1	34	578			1,094	20, 739	136	2, 512
	12, 195	309, 382	36, 164	943, 385	18, 147	394, 882	13, 072	276, 088

<sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

### WORLD PRODUCTION

Reports from some foreign countries indicate that peat is being used extensively as fuel; however, complete production data cannot be obtained until after the war. The following table shows available statistics on world output of peat, 1938-42.

World production of peat, 1938-42, by countries 1 [Compiled by B. B. Waldbauer]

Country 1	1938	1939	1940	1941	1942
Canada:		J. 2. 4			
Fuel metric tons	454	404	27	322	191
Peat mossdo		(2)	15, 591	25, 222	40, 747
Denmark dodo	(2) (3) (2)	2	8 2, 500, 000	8 2, 500, 000	3 4, 600, 000
Eiredo	25	2	(2)	5, 398, 274	(3)
Estonia do do	185, 600	22	(2)	(2)	2
Finland do	(2)	(2)	3 30,000	\$ 100,000	3 200, 000
Latvia:			00,000	- 100,000	200,000
Littercubic meters_	90, 369	80,000	(2)	(2)	(2)
Wastedo	14, 901	20,000	2	2	2
Insulationdo	2, 440	3,000	25	}₂⟨	2
Lithuania metric tons	180,000	230,000	(2)	/2√	(2)
Netherlandsdo	800,000	822, 400	842,000	25	2
Norwaydodo	(2)	(2)	(2)	4 60,000	4 120,000
Sweden:				00,000	- 120,000
Fueldo	25, 711	22, 953	3 25,000	3 400, 000	3 1,000,000
Litter, baleddo	99, 998	(2)	(2)	(2)	(2)
Litter and "mull," unbaled		` ` `		` ' '	
cubic meters	36, 578	(2)	(2)	(2)	(2)
"Mull," baledmetric tons_	31, 959	(2)	(2)	(2)	(2)
Switzerlanddo	10,000	ìź, 000	ìź, 000	(2)	(2)
U. S. S. R	26, 460, 700	(2)	(2)	(2)	(2)
United Statesdo	41,669	<b>5</b> 0, 333	63, 591	78, 474	64, 863

In addition to countries listed Argentina, Austria, France, Germany, Hungary, Italy, and Poland produce peat, but data of production are not available.
 Data not available.
 Estimated.

<sup>4</sup> Estimated production of a factory at Vigra, near Aalesund.

## CRUDE PETROLEUM AND PETROLEUM PRODUCTS<sup>1</sup>

BY A. G. WHITE, G. R. HOPKINS, H. A. BREAKEY, AND A. T. COUMBE

#### SUMMARY OUTLINE

	Page		Page
General review	1025	Refined products—Continued.	
Salient statistics	1027	Marketing	_ 1084
Reserves	1031	Motor fuel	. 1085
Legislation and administration	1033	Domestic demand	
Proration	1034	Exports	_ 1087
ProrationCrude petroleum	1035	ProductionYields	_ 1088
Supply and demand	1035	Yields	_ 1090
Production	1036	Prices	1090
General	1036	A viation gasoline	1092
By States	1039	Stocks	_ 1092
Wells	1056	Production and consumption by	
Stocks	1058	States	1095
Consumption and distribution		Distribution	1096
Runs to stills		Kerosine and range oil	1098
Distribution	1062	Fuel oil	_ 1101
Prices and value	1009	Lubricating oil	. 1114
Refined products	1071	Other products	_ 1117
General review	1071	World production	_ 1121 _ 1128
Refining	1081	Foreign trade	
Refinery capacity	1081		
Technical developments	1082	Exports Intercoastal shipments	- 112 <b>9</b>
Transportation	1083	l lillercoasiai siiidiieliis	

#### GENERAL REVIEW

Outstanding effects of the war on the supply and demand for all oils in 1942 were the sharp decline in civilian gasoline demand owing to the necessity of conserving both tires and motor vehicles; the readjustments in refinery operations and yields resulting from the drop in gasoline demand and the rise in fuel-oil requirements; a major recession in imports, accompanied by a substantial gain in exports; the drastic curtailment of oil consumption in the Atlantic Coast States resulting from the diversion of tankers to war uses and the substitution of new overland transport routes; and the large increase in the total demand for oil in the Pacific Coast district.

The total demand for all oils reached a peak of 1,595 million barrels in 1941 and decreased about 32 million barrels (2 percent) in 1942. The principal changes compared with 1941 were a drop of 72 million barrels in the total demand for motor fuel, a gain of almost 20 million barrels in the total demand for residual fuel oil, and an increase of 17 million barrels in the demand for distillate fuel oil. The decline in total demand would have been greater except for liquidation of almost 37 million barrels of stocks of refined oils in areas where normal transportation facilities were sharply curtailed. In the East Coast district such stocks were reduced almost to bare working levels. view of the large increases in the direct war demands for oil products, a substantial increase in total demand might have been expected in 1942 rather than a decrease. To visualize the effect of various restrictions on civilian consumption properly it would be necessary to set up an estimated normal demand for 1942 rather than to make direct comparisons between actual 1941 and 1942 data.

THE TAX ST. CO. S. C. S.

<sup>1</sup> Data for 1942 are preliminary; detailed statistics with final revisions will be released later.

The progressive readjustment in refinery operations in 1942 resulted from a 5-percent decline in the amount of crude refined as well as from the substantial gain in fuel-oil demand and the sharp reduction in gasoline demand. This situation was complicated further by a 62-million barrel drop in imports, consisting primarily of heavy crude and fuel oils. As the result of these various factors, the average yield of gasoline was reduced 4.5 percent, whereas the yield of residual fuel oil was increased 2.6 percent and that of distillate fuel 1.3 percent.

The production of crude petroleum totaled 1,385 million barrels in 1942, and the demand for domestic crude petroleum amounted to 1,395 million barrels. Compared with 1941, there was a decline of 17 million barrels in crude production and a decrease of 26 million barrels in crude demand. The recession in total demand for all oils and the large withdrawals from refined stocks tended to reduce the demand for domestic crude petroleum, but the effect was largely offset by the sharp drop in total imports.

Total demand for all oils in the United States, 1933-42, [Millions of barrels].

Year	Domestic demand	Exports	Total demand	Year	Domestic demand	Exports	Total demand
1933	868. 5	106. 7	975. 2	1938	1, 137. 1	193. 7	1, 330. 8
	920. 2	114. 5	1, 034. 7	1939	1, 231. 1	188. 9	1, 420. 0
	983. 7	129. 0	1, 112. 7	1940	1, 326. 6	130. 5	1, 457. 1
	1, 092. 7	132. 0	1, 224. 7	1941	1, 485. 8	108. 8	1, 594. 6
	1, 169. 7	172. 8	1, 342. 5	1942	1, 442. 0	121. 1	1, 563. 1

<sup>1</sup> Subject to revision.

The combined demand for motor fuel, residual fuel oil, and distillate fuel oil represents about 80 percent of the total demand for all oils. A brief review of the demand and supply trends for these three products will reflect the most significant changes in the oil situation in

1942 compared with 1941.

The total demand for motor fuel declined from 695 million barrels in 1941 to 622 million in 1942—a 10-percent decrease. The average yield of gasoline from crude petroleum fell from 44.2 percent in 1941 to 39.7 percent in 1942. The refinery output was supplemented by a reduction of over 15 million barrels in finished gasoline stocks compared with an increase of over 8 million barrels in 1941. Exports of motor fuel rose from 27 million barrels in 1941 to 36 million in 1942, and domestic demand decreased from 667 million barrels in 1941 to 586 million in 1942. As the rapidly expanding military requirements for gasoline are included in domestic demand, the decline in civilian consumption was materially greater than the total decline in domestic According to the best estimates available, the decline in the civilian automotive use of motor fuel in 1942 was about 105 million barrels or approximately 18 percent. In evaluating the actual effect of the curtailment in civilian consumption, this decline might reasonably be compared with an expectation of at least a 5 percent normal increase in 1942 based upon the increase in the number of motor vehicles in use on January 1, 1942, compared with January 1, 1941. As the total indicated decline in gasoline demand in the Eastern States (Petroleum Administration for War District 1) was about 46 million barrels in 1942, it would appear that about half of the total national decline in civilian automotive use occurred in that area.

The total demand for residual fuel oil rose to 417 million barrels in 1942—a gain of almost 20 million barrels or 5 percent compared with 1941. This increase was all in domestic demand, as exports showed a small decline. Three major changes of about equal importance featured domestic demand. Railroad consumption increased by about 20 million barrels, the rise in naval requirements was probably of similar magnitude, and a decline of about the same amount is indicated as the result of conversions to coal and rationing. On the supply side, imports were 20 million barrels less; withdrawals from storage rose from 5 million barrels in 1941 to 21 million in 1942: transfers from crude to residual were 6 million barrels greater; and refinery production increased from 342 million barrels in 1941 to 359 million in 1942, with an increase in yield from 24.3 percent to 26.9 percent.

Salient statistics of crude petroleum, refined products, and natural gasoline in the United States, 1938-42

	1938	1939	1940	1941	19421
Prude petroleum:					
Domestic productionthousands of barrels 2 World productiondo United States proportion of world production	1, 988, 041	1, 264, 962 2, 085, 444	1, 353, 214 2, 141, 721	1, <b>402</b> , 228 2, 212, 332	1, 385, 479 2, 054, 318
Imports 3thousands of barrels 2 _ Exportsdo Stocks, end of period:	26 412	33, 095		50,606	12, 297 33, 834
Gasoline-bearing crudedo	274, 165	239, 978	264, 079	247, 499 246, 884	234, 354
California heavy crude do Runs to stills do Total value of domestic production at wells thousands of dollars.	16, 467 1, 165, 015	13, 330 1, 237, 840	11, 906 1, 294, 162	10, 179	10, 865 1, 333, 769
thousands of dollarsverage price per barrel at wells	1, 373, 060 \$1. 13	1, 294, 470 \$1. 02	1, 385, 440 \$1. 02	1, 602, 000 \$1. 14	61, 620, 000 6\$1. 17
Dec. 31  Total oil wells completed in the United States	369, 640	380, 390	389, 010	399, 960	(7)
during year	18, 433	17, 485	19, 125	19, 195	10, 302
large defined products:  Imports 4	27, 896 116, 474	25, 965 116, 883	41, 089 78, 970	46, 536 75, 592	22, 777 87, 295
Stocks, end of perioddo	272, 241	268, 109	282, 265 280, 958	290, 375 5 294, 310	247, 554
Output of motor fueldo Yield of gasolinepercent Completed refineries, end of year	569, 162 44. 3 538	611, 043 45. 0 547	616, 695 43. 1 556	701, 294 44. 2 522	607, 011 39. 7 471
Daily crude-oil capacity of refineries thousands of barrels 2	4, 509	4, 629	4, 719	4, 957	4, 899
Average dealer's net price (excluding tax) of gaso- line in 50 United States citiescents per gallon 8 latural gasoline:	10. 04	9. 58	9.08	9. 49	10. 44
Productionthousands of barrels 2	51, 347	51, 650	55, 700	80,855	83, 567
Stocks, end of perioddo	4, 830	4, 421	5, 704	4, 275 5 4, 437	4, 632

Subject to revision.

42 gallons.

The total demand for distillate fuel oil increased from 190 million barrels in 1941 to 207 million in 1942—a 9-percent gain. rose from 17 million barrels to 23 million and domestic demand from 173 million barrels to 184 million. About 70 percent of the total domestic demand is used for heating purposes. In view of the larger number of oil-heating installations in use in 1942, a substantial

As reported to the Bureau of Mines.
Department of Commerce; exports include shipments to noncontiguous Territories.
For comparison with succeeding year.

Estimated.

Figures not available.
American Petroleum Institute.

increase in demand was anticipated, but this expected gain was reduced by the rationing program effective in the last quarter of 1942. principal changes in supply in 1942 were a decrease of about 2 million barrels in imports, a reduction of over 4 million barrels in stocks compared with a stock increase of 7 million in 1941, and a gain of about 8 million barrels in refinery production with an increase in yield from 13.4 percent in 1941 to 14.7 percent in 1942.

From a regional viewpoint, the outstanding changes in oil demand in 1942 were the rapid rise in demand in the Pacific Coast district and the sharp curtailment in normal consumption in the Atlantic Coast States. California was the main source of oil supply for war operations in the Pacific and an important supplier of fuel for expanding war industries and increasing railroad traffic. The Atlantic Coast area consumed about 38 percent of the total demand for all oils in 1941 and felt the full effect of the major disturbances in trans-

portation in 1942.

The increase in the total demand for all oils in the Pacific Coast area has been one of the major results of the changes due to the war. The demand for all oils approximated 246 million barrels in both 1939 and 1940. It rose to 256 million barrels in 1941 and to 279 million in 1942. Exports and noncontiguous shipments have dropped steadily from 61 million barrels in 1939 to 23 million in 1942. Shipments by boat and rail to States outside the Pacific Coast market area have likewise slumped from about 11 million barrels in 1939 to 3 million in 1942. This sharp reduction in outside shipments has been much more than offset by the rapid increase in railroad, war industry, and military and naval requirements in the five States constituting the dometic market area. This domestic demand has increased from about 174 million barrels in 1939 to 213 million in 1941 and 253 million in 1942. The major factor in the 40-million-barrel gain in domestic demand in 1942 was the 28-million-barrel increase in the demand for heavy fuel oils. The production of crude petroleum in 1942 was 24 million barrels above the 1939-40 level and was supplemented by a withdrawal from stocks of all oils of about 12 million barrels.

In contrast with the sharp rise in oil demand in the Pacific Coast district, the war has brought a severe curtailment of consumption in the Atlantic Coast States. The indicated demand for all oils in this area (Petroleum Administration for War District 1) fell from 607 million barrels in 1941 to 509 million in 1942—a decline of 98 million barrels (16 percent). In normal times, the major part of the supply was delivered by boat from the Gulf coast and from foreign sources. The diversion of tankers to war uses shifted the burden of transportation to new overland routes that required organization of a huge tank-car movement, construction of new pipe lines, and increased use of inland waterways. The total indicated demand for motor fuel rose from 214 million barrels in 1940 to 236 million in 1941 and was reduced to about 190 million in 1942—a decline of 19 percent for the Compared with 1941, gasoline consumption during the first quarter of 1942 showed a slight gain but was reduced by 23 percent in the second quarter, by 28 percent in the third quarter, and by 23 percent in the fourth quarter. A sharp reduction in deliveries to distributors was followed by inauguration of a gasoline-rationing system in May that reduced civilian consumption more drastically

than in other districts, where rubber conservation was the main

objective.

The supply of residual fuel oil presented a problem second only to that of motor fuel. The long-distance movements of residual oil depended on tanker transport, owing to lower cost and the inherent difficulty of moving this heavy product by either tank car or pipe line. A program was begun early in the year to urge industrial consumers to convert from fuel oil to coal, and these conversions had reached an annual rate of over 30 million barrels in District 1 by the end of the year. The alarming depletion of the total stocks of all oils led to establishment, on October 1, of a system for rationing heating oils in both the Atlantic Coast area and in the Middle West. Although the cumulative effect of these measures made it possible to meet the most essential requirements during the winter months, an adequate civilian supply for this district remains one of the acute problems in 1943.

A brief review of the major factors in the trend of oil supply and demand, by quarters, beginning with the last quarter of 1941 and extending through the first quarter of 1943, will give a better perspective of the results of increasing war requirements and of progressive

restrictions on less essential civilian uses.

The demand for all oils reached an all-time peak of 422 million barrels in the last quarter of 1941, with daily average crude production at a peak of 4,107,000 barrels and crude runs at a peak of

4,058,000 barrels daily for the quarter.

The total demand for all oils dropped to 408 million barrels in the first quarter of 1942, but this amount was still almost 11 percent greater than for the same period in 1941. War requirements were increasing, and the need for curtailing civilian demands was just becoming apparent. The decline in imports was relatively small, and demand was sustained further by a reduction of over 27 million barrels in the stocks of refined oils, compared to a liquidation of only 7 million barrels for the same period of 1941. Compared with the first quarter of 1941, average runs to stills gained 146,000 barrels daily and crude production 366,000 barrels daily, although about one-half of this increase was reflected in a rise in crude stocks. The total demand for motor fuel increased by almost 5 percent, for residual fuel oil by over 12 percent, and for distillate fuel oil by almost 12 percent.

In the second quarter of 1942 the effects of the disturbance in normal transportation and the necessity of conserving rubber became The demand for all oils was almost 3 percent less more apparent. than in the same period of 1941. Imports declined 16 million barrels, refined stocks were reduced almost 21 million barrels, and crude stocks dropped over 11 million barrels. Compared with the second quarter of 1941, average runs to stills decreased 323,000 barrels daily and crude production 203,000 barrels daily. The reduction of almost 11 percent in the total demand for motor fuel was the major factor, accompanied by smaller relative gains of 6 percent in the total demand for residual fuel oil and about 9 percent for distillate fuel oil. With rapidly dwindling stocks and reduced tanker movements, the supply situation in the East coast became a serious problem, and steps were taken to restrict civilian consumption of motor fuel and to urge industrial plants using fuel oil to convert to coal.

## Supply and demand of all oils in the United States in 1942, by months [Including wax, coke, asphalt, and still gas, in thousands of barrels]

						1942 1						1941		
	Jan.	Feb.	Mar.	April	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total	(total)
New supply:														
Domestic production: Crude petroleum Natural gasoline Benzol	128, 262 7, 488 208	113, 961 6, 768 189	114, 473 7, 020 200	105, 053 6, 257	110, 192 6, 718	108, 595 6, 558	111, 782 6, 804	120, 429 7, 028	115, 801 6, 998	120, 311 7, 256	116, 101 7, 156	120, 519 7, 516	1, 385, 479 83, 567 597	1, 402, 228 80, 858 3, 438
Total productionImports:	135, 958	120, 918	121, 693	111, 310	116, 910	115, 153	118, 586	127, 457	122, 799	127, 567	123, 257	128, 035	1, 469, 643	1, 486, 518
Crude petroleum Refined products	3, 554 3, 933	3, 068 4, 009	2, 058 3, 496	1, 109 1, 894	849 739	540 437	135 637	315 829	236 601	111 2,450	74 1,964	248 1,788	12, 297 22, 777	50, 606 46, 536
Total new supply, all oils	143, 445 -2, 519	127, 995 +2, 691	127, 247 -9, 874	114, 313 -13, 552	118, 498 -8, 200	116, 130 -9, 224	119, 358 -7, 353	128, 601 +5, 862	123, 636 -1, 591	130, 128 -470	125, 295 -9, 047	130, 071 -5, 128	1, 504, 717 -58, 405	1, 583, 660 -10, 949
Demand: Total demand Exports:	145, 964	125, 304	137, 121	127, 865	126, 698	125, 354	126, 711	122, 739	125, 227	130, 598	134, 342	135, 199	1, 563, 122	1, 594, 609
Crude petroleum Refined products	1, 522 6, 761	1, 336 5, 238	1,887 7,139	2, 973 7, 139	3, 709 6, 097	3, 591 7, 775	3,370 10,780	4, 073 6, 680	3, 240 5, 702	3, 264 9, 026	2,826 6,818	2,043 8,140	33, 834 87, 295	33, 238 75, 592
Domestic demand: Motor fuel. Kerosine. Distillate fuel oil. Residual fuel oil. Lubreating oil. Miscellaneous.	49, 223 9, 750 24, 981 37, 701 2, 680 13, 346	42, 415 7, 690 21, 671 34, 275 2, 453 10, 226	50, 440 7, 230 18, 517 36, 803 2, 615 12, 490	49, 396 5, 516 13, 769 34, 109 2, 781 12, 182	52, 512 4, 580 11, 191 31, 414 2, 525 14, 670	49, 945 3, 653 11, 187 31, 040 2, 665 15, 498	54, 228 3, 266 6, 987 30, 104 1, 962 16, 014	48, 606 4, 039 10, 649 30, 600 2, 128 15, 964	49, 828 5, 012 13, 800 30, 442 2, 267 14, 936	49, 793 5, 367 13, 050 33, 830 2, 112 14, 156	50, 413 5, 684 15, 900 35, 376 2, 598 14, 727	39, 289 7, 827 22, 610 37, 779 2, 232 15, 279	586, 088 69, 614 184, 312 403, 473 29, 018 169, 488	667, 505 69, 469 172, 824 383, 422 30, 255 162, 304
Total domestic demand	137, 681	118, 730	128, 095	117, 753	116, 892	113, 988	112, 561	111, 986	116, 285	118, 308	124, 698	125, 016	1, 441, 993	1, 485, 779
Stocks:							100							
Gasoline-bearing crude in U. S	253, 531 10, 543	260, 844 11, 229	261, 832 11, 737	257, 761 11, 434	254, 577 11, 168	251, 421 10, 892	245, 026 10, 950	244, 125 10, 706	240, 043 10, 167	237, 361	234, 100	234, 354	234, 354	$\left\{ \begin{array}{c} 247,499\\ {}^{2}246,884 \end{array} \right.$
Natural gasoline	4, 802	5, 209	5, 620	6,043	6, 568	6, 517	6, 588	6, 405	6, 056	10, 868 5, 424	10, 724 4, 996	10,865 4,632	10, 865 4, 632	10, 179 4, 275
Refined products	284, 415	278, 700	266, 919	257, 318	252, 043	246, 302	245, 215	252, 405	255, 784	257, 927	252, 713	247, 554	247, 554	$ \left\{ \begin{array}{c} 24,437 \\ 290,375 \\ 2294,310 \end{array} \right. $
Total, all oils	553, 291	555, 982	546, 108	532, 556	524, 356	515, 132	507, 779	513, 641	512, 050	511, 580	502, 533	497, 405	497, 405	552, 328 2 555, 810

i Subject to revision.

<sup>&</sup>lt;sup>2</sup> Preliminary figures for Jan. 1, 1942.

In the third quarter of 1942, the demand for all oils was 9 percent less than in the same period of 1941. Imports were almost 23 million barrels less. Efforts to rebuild depleted stocks of refined oils resulted in a gain of about 10 million barrels, but crude stocks were reduced further by 12 million barrels. Although crude runs and crude production were substantially above the low levels of the second quarter, the daily average was still 305,000 and 112,000 barrels, respectively, below the third quarter of 1941. The total demand for motor fuel showed a relative decline of 17 percent from the previous year, while the gain in residual demand was less than 5 percent and for distillate fuel oil only 6 percent. A gasoline-rationing system was inaugurated in May in the Eastern States, restrictions were placed on the distribution of distillate fuel oil, and further conversions of industrial plants from oil to coal became effective.

The total demand for all oils was only about 5 percent less in the last quarter of 1942 than in the same period of 1941. Imports were 22 million barrels less than in 1941. Crude production and runs to stills continued to rise, but the daily averages were, respectively, 228,000 and 340,000 barrels daily below the all-time peaks of the last quarter of 1941. The total demand for gasoline showed a relative decline of over 15 percent, whereas the demand for residual fuel oil increased only 2 percent and for distillate fuel oil about 8 percent above the previous year. Gasoline rationing was established on a Nationwide basis in December, but its effect on total demand was obscured by heavy advance stocking by consumers. Inauguration of the rationing of heating oils in the main consuming areas on October 1 reduced potential demand materially, but the effect was modified by the substantial gain in the number of installations compared with the previous The small gain in residual demand indicated that the large increases in naval and railroad consumption were largely offset by the cumulative effect of conversions to coal, of increased prices, or of actual inability to procure adequate supplies in some districts.

The total demand for all oils in the first quarter of 1943 was about 9 percent less than in the same period of 1942 but was almost 1 percent greater than the comparatively low level of the first quarter of 1941. For the succeeding quarters of 1943, total demand may exceed the 1942 levels, as war requirements and exports progressively increase and as civilian consumption reaches essential minimum levels.

#### RESERVES

Reserves of crude oil on January 1, 1943, were estimated by the American Petroleum Institute Committee on Petroleum Reserves at 20,082,793,000 barrels. These reserves include only crude oil and distillate in known and proved fields and recoverable by present production methods. Additions to reserves during 1942 totaled 1,878,976,000 barrels; but only 260,051,000 barrels represented new pools discovered during the year, and 1,618,925,000 barrels represented upward revisions of reserve estimates for fields discovered before 1942. Although estimated reserves are more than 14 times the amount of petroleum produced in the peak year 1941, warnings of a shortage are increasing. It was pointed out that if the demands for this nation and its allies increased materially, new discoveries would be necessary to supply these requirements and yet keep within an efficient rate of production.




FIGURE 1.—Supply and demand of all oils in the United States, 1918-42.

Estimates of proved oil reserves in the United States on Jan. 1, 1937-43, by States 1
[Millions of barrels]

Eastern States:	State	1937	1938	1939	1940	1941	1942	1943
Hilinois	~ ~ ~							
Indiana			41	049	200	215	224	307
Rentucky								32
Michigan         44         49         43         51         35         56         60           New York         66         61         41         35         65         60           Ohio         32         28         26         32         30         37           Pennsylvania         307         288         200         183         188         171           West Virginia         32         28         24         46         53         50           551         536         621         787         741         767           Central and Southern States:         84         192         188         320         306         295           Kansas         568         601         613         726         692         690         692         690           Louisiana         524         714         1,040         1,173         1,216         1,330         80         692         690           New Mexico         47         547         703         687         675         675         675         675         675         675         675         675         675         675         675         675         675								35
New York								64
Ohio         32         28         26         32         30         37           Pennsylvania         307         288         200         183         188         171           West Virginia         32         28         24         46         53         50           551         536         621         787         741         767           Central and Southern States:         84         192         188         320         306         295           Kansas         568         601         613         726         692         660         620           Louisiana         524         714         1,040         1,173         1,216         1,330         7         40         80	Michigan	44						54
Pennsylvania         307         288         200         183         188         171           West Virginia         32         28         24         46         53         50           551         556         621         787         741         767           Central and Southern States:         Arkansas         84         192         188         320         306         295           Kansas         568         601         613         726         692         690         690         1,173         1,216         1,330         7         40         80 <t< td=""><td></td><td></td><td></td><td></td><td></td><td></td><td></td><td>35</td></t<>								35
West Virginia         32         28         24         46         53         50           Central and Southern States:         551         536         621         787         741         767           Central and Southern States:         4         192         188         320         306         295           Kansas.         568         601         613         726         692         690           Louisiana         524         714         1,040         1,173         1,216         1,330           Mississippi         7         40         80         887         692         675           Oklahoma         1,141         1,212         1,162         1,063         1,002         1,036           Texas         6,422         8,248         9,448         9,768         10,624         10,976           9,210         11,514         13,154         13,744         14,572         15,082           Mountain States:         15         19         18         20         23         23           Colorado         15         19         18         20         23         23           Wyoming         239         266         261	Ohio							
Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   States   Solution   Solution   Solution   States   Solution   Solution   Solution   States   Solution   Pennsylvania							153	
Central and Southern States:  Arkansas	West Virginia	32	28	24	46	53	50	47
Arkansas         84         192         188         320         306         295           Kansas         568         601         613         726         692         690           Louisiana         524         714         1,040         1,173         1,216         1,330           Mississippi         7         40         80         70         887         692         675           Oklahoma         1,141         1,212         1,162         1,063         1,002         1,036           Texas         6,422         8,248         9,448         9,768         10,624         10,976           Mountain States:         15         19         18         20         23         23           Montana         92         109         105         94         89         86           Wyoming         239         266         261         306         305         304           Pacific Coast States: California         2,956         3,063         3,189         3,532         3,291         3,333		551	536	621	787	741	767	727
Kansas	Central and Southern States:			1 A 1 A				
Louisiana	Arkansas	84						300
Louisiana	Kansas	568		613	726			687
New Mexico	Louisiana	524	. 714	1,040	1,173	1, 216		1, 442
Oklahoma         1, 141         1, 212         1, 162         1, 063         1, 002         1, 036           Texas         6, 422         8, 248         9, 448         9, 768         10, 624         10, 976           9, 210         11, 514         13, 154         13, 744         14, 572         15, 082           Mountain States:         15         19         18         20         23         23           Montana         92         109         105         94         89         86           Wyoming         239         266         261         306         305         304           Pacific Coast States: California         2, 956         3, 063         3, 189         3, 532         3, 291         3, 333	Mississippi				7			41
Oklahoma     1, 141     1, 212     1, 162     1, 063     1, 002     1, 036       Texas     6, 422     8, 248     9, 448     9, 768     10, 624     10, 976       9, 210     11, 514     13, 154     13, 744     14, 572     15, 082       Mountain States:     15     19     18     20     23     23       Montana     92     109     105     94     89     86       Wyoming     239     266     261     306     305     304       Pacific Coast States: California     2, 956     3, 063     3, 189     3, 532     3, 291     3, 333	New Mexico							677
9,210   11,514   13,154   13,744   14,572   15,082	Oklahoma	1, 141	1,212	1, 162	1,063	1,002	1,036	969
Mountain States:  Colorado	Texas	6, 422	8, 248	9,448	9,768	10,624	10, 976	11, 546
Colorado		9, 210	11,514	13, 154	13, 744	14, 572	15, 082	15, 662
Montana. 92 109 105 94 89 86 Wyoming 239 266 261 306 305 304 Pacific Coast States: California. 2,956 3,063 3,189 3,532 3,291 3,323	Mountain States:							
Wyoming         239         266         261         306         305         304           Pacific Coast States: California         2,956         3,063         3,189         3,532         3,291         3,333	Colorado					23		39
Pacific Coast States: Califor- 118	Montana							86
Pacific Coast States: Califor- nia	Wyoming	239	266	<b>2</b> 61	306	305	304	370
nia 2,956   3,063   3,189   3,532   3,291   3,323		346	394	384	420	417	413	495
		2, 956	3,063	3, 189	3, 532	3, 291	3, 323	3, 197
							4	2
Total United States 13,063 15,507 17,348 18,483 19,025 19,589	Cotal United States	13, 063	15, 507	17, 348	18, 483	19,025	19, 589	20, 083

<sup>&</sup>lt;sup>1</sup> From reports of Committee on Petroleum Reserves, American Petroleum Institute, of the amount of crude oil that may be extracted by present methods from fields completely developed or sufficiently explored to permit reasonably accurate calculations. The change in reserves during any year represents total new discoveries, extensions, and revisions minus production.

#### LEGISLATION AND ADMINISTRATION

Among the legislation affecting the petroleum industry was the O'Mahoney Act, signed December 24. This act, although passed too late to influence operations in 1942, is designed to promote exploration on public lands. It provides a flat 12½-percent royalty for 10 years on all oil and gas produced from new wells in newly discovered fields on public lands in place of the "Step-scale rates" provided for in the act of 1935. Another law suspends antitrust action on acts done to further the war program, and yet another gives the Army and Navy pewor to force reductions in patent royalties.

Administrative orders by agencies appointed by the President put the petroleum industry under wartime regulation. The principal agencies involved were the Office of Defense Transportation, the Office of Price Administration, and the Office of Petroleum Coordinator (changed toward the end of the year to Petroleum Administration

for War).

The Petroleum Administration for War, in addition to being made a claimant agency (an agency that has the right to claim a priority on scarce material), was given the power to issue instructions and orders relating to all phases of the industry and the means for enforcing such instructions and orders.

Office of Petroleum Coordinator Conservation Order M-68 and War Production Board Preference Rating Order P-98 were two im-

portant regulatory measures in effect during 1942. The former limited drilling, with exceptions, to one well to each 40 acres and provided for easy acquisition of drilling and operating material and supplies by operators who conform to the regulation. This order eliminated the drilling of an estimated 13,000 wells, with the result that the use of steel for drilling in defined fields was reduced to 60 percent of that in Even greater curtailment is promised in future, with a much

wider spacing pattern.
Preference Rating Order P-98 enabled oil operators to get priority ratings on scarce material under the Priorities Rating Plan (PRP). The Controlled Materials Plan (CMP), a new plan for distributing scarce materials, came into use January 1, 1943, 6 months being allowed for the transition period from the old PRP to the CMP. Under the CMP certain agencies, designated as claimant agencies, submit requirements for scarce material to the Controlled Materials Division of the War Production Board. The Controlled Materials Division then analyzes the requirement claims and makes allotments to the claimant agencies through its Requirements Committee, which is made up of representatives from each of the claimant agencies, in addition to one from the Department of State. Claimant agencies then distribute the allotments to the qualified consumers. Petroleum Administration for War was made a claimant agency under this plan.

Office of Petroleum Coordinator Directive 59 called for the joint use of facilities among persons engaged in the petroleum industry and the joint use of their products in Districts 1, 2, and 3. It was designed to eliminate crosshauling and to assure, as far as possible, an equitable proportion of stocks and of sales among the supplies in each area. These acts, illegal under the Sherman antitrust law, were approved by legislation passed in 1942 suspending antitrust action

on acts done to further the war program.

Other administrative acts affecting the petroleum industry included prohibition of the use of tank cars in the Midwest; prohibition of use of tin, terneplate, and blackplate for motor-oil cans; prohibition of gasoline shipments from the East coast; prohibition of use of benzene in motor fuel; prohibitions on the use of asphalt and road oil; placing of butadiene under allocation control; setting Nation-wide automobile speed limit, first at 40 miles per hour then at 35; making United States refining processes available to Russia; directing the shipments of specific quantities of products from Districts 2 and 3 to District 1; modifying refinery yields; prohibition of manufacture of domestic oil burners; prohibition of movement of gasoline to East coast by tank car in favor of fuel oil; and prohibition of use of credit cards for gasoline.

PRORATION

Early in 1942 the Office of Petroleum Coordinator assumed the function of prescribing the rates of crude-oil production for the States in place of the estimates of market demand that had been issued by the Bureau of Mines theretofore. The Bureau of Mines continued to issue the monthly forecast of motor fuel and crude-oil requirements and to supply the Office of Petroleum Coordinator with estimates of the market demand for crude oil for the individual States. Production recommendations by the Office of Petroleum Coordinator included consideration of reserves and of efficient production rates as well as market demand. Beginning in April, recommendations for production comprised all petroleum liquids, including con-

densate and natural-gas derivatives as well as crude oil.

Proration in the past generally has been based upon dividing the production determined necessary, so that each well received its share based upon the proration formula in effect. Thus a purchaser might be required to fill part of his needs with an oil that he did not desire because the proration theory required that the demand be divided proportionately among all the oils. War conditions, however, changed this aspect of proration in 1942, and wells producing crudes suitable for aviation gasoline, high-grade lubricants, and other military requirements were given preference.

The Interstate Oil Compact Commission voted at the December

meeting to extend the life of the compact to September 1, 1947.

The table usually appearing in this section showing market-demand estimates, State allowables, and production has been suspended because Petroleum Administration for War certified production rates, which have supplanted the Bureau of Mines estimates of market demand, include natural gasoline and distillates and are not comparable with crude-oil production.

## CRUDE PETROLEUM SUPPLY AND DEMAND

The total demand for crude petroleum was approximately 1,410 million barrels in 1942, compared with 1,472 million in 1941—a reduction of about 62 million barrels or 4 percent. This decline was due to a drop in the total demand for all oils and an abnormal liquidation of stocks of refined oils. A 75-million-barrel decrease in crude runs to stills was partly offset by a 13-million-barrel rise in crude used for fuel and losses and a slight gain in crude exports. Compared with 1941, domestic crude production declined by about 17 million barrels, crude imports were reduced by 38 million barrels, and total withdrawals from crude stocks were only 12 million barrels or 7 million less than in 1941.

Supply of and demand for crude petroleum in the United States, 1938-42 [Thousands of barrels]


	1938	1939	1940	1941	1942 1
Production	1, 214, 355 26, 412	1, 264, 962 33, 095	1, 353, 214 42, 662	1, 402, 228 50, 606	1, 385, 479 12, 297
Changes in stocks 3	-28, 913 1, 269, 680	-37, 314 1, 335, 371	+23, 307 1, 372, 569	-18, 942 1, 471, 776	-11, 844 1, 409, 620
Runs to stills:	1, 138, 828	1, 204, 350	1, 252, 364	1, 358, 246	1, 319, 173
Foreign Exports	26, 187 77, 254	33, 490 72, 076	41, 798 51, 496	50, 946 2 33, 238	14, 596 2 33, 834
Transfers to fuel oil: Pipe-line operations east of California Other transfers	1, 930 12, 112	2, 125 10, 284	2, 297 7, 978	2, 383 13, 099	2, 484 19, 255
Other fuel and losses	13, 369	13, 046	16, 636	13, 864	20, 278
Total demand	1, 269, 680	1, 335, 371	1, 372, 569	1, 471, 776	1, 409, 620

<sup>&</sup>lt;sup>1</sup> Subject to revision.

As reported to Bureau of Mines.
Inclusive of heavy crude in California.

#### PRODUCTION

General.—Crude-oil output of 1,385,479,000 barrels was 16,749,000 barrels less than the 1,402,228,000 produced in 1941. Greatest declines were in Illinois—25,937,000 barrels; Texas—22,201,000; and Oklahoma—14,012,000. Production increased 18,063,000 barrels in California and 14,394,000 in Kansas.



TOURE 2.—Daily average production of crude petroleum, total number of oil wells completed, and average price per barrel of a selected grade of Oklahoma crude petroleum in the United States, 1934-42, by months.

Petroleum produced in the United States, 1938-42, and total, 1859-1942, by States1 [Thousands of barrels]

				<u> </u>		
	1938	1939	1940	1941	1942 2	1859-1942 (total)
Production:						
Arkansas	18, 180	21, 238	25, 775	26, 327	26, 628	559, 37
California	249, 749	224, 354	223, 881	230, 263	248, 326	6, 048, 66
Colorado	1,412	1,404	1,626	2, 150	2, 220	44, 26
Illinois	24, 075	94, 912	147, 647	132, 393	106, 456	938, 52
Indiana	995	1,711	4,978	7, 411	6,743	145, 26
Kansas	60,064	60, 703	66, 139	83, 242	97, 636	3 1,301, 81
Kentucky	5, 821	5, 621	5, 188	4,762	4, 472	4 176, 39
Louisiana	95, 208	93, 646	103, 584	115, 908	115, 726	1, 291, 6
Michigan	18, 745	23, 462	19, 753	16, 359	21, 754	5 183, 2
Mississippi		107	4,400	15, 327	28, 833	48, 6
Montana	4, 946	5, 960	6,728	7, 526	8, 074	
Nebraska		2	276	1,898	1, 237	3, 4
New Mexico	35, 759	37, 637	39, 129	39, 569	31, 544	6 345, 8
New Mexico New York	5, 045	5,098	4,999	5, 185	5, 421	7 129, 3
Ohio	3, 298	3, 156	3, 159	3, 510	3, 543	595, 4
Oklahoma	174, 994	159, 913	156, 164	154, 702	140, 690	3 5,101, 5
Pennsylvania	17, 426	17, 382	17, 353	16, 750	17, 779	7 1,031, 5
Texas	475, 850	483, 528	493, 209	505, 572	483, 371	7, 568, 7
West Virginia	3, 684	3, 580	3, 444	3, 433	3, 574	417, 7
Wyoming		21, 454	25, 711	29,878	31, 392	562, 2
Other States 8	82	94	71	63	60	1, 2
Total, United States	1 914 255	1 264 069	1 252 014	1 400 000	1 205 470	00 504 1
alue at wells:	1, 214, 300	1, 204, 902	1, 505, 214	1, 402, 228	1, 385, 479	26, 594, 1
Total (thousands of dollars)	1 272 060	1 904 470	1 905 440	1 600 000	1 600 000	21 205 2
Average per barrel	\$1.13	21, 234, 470				
WACTURE DEL DUTTET	φ1.13	\$1.02	\$1.02	\$1.14	\$1.17	\$1.

<sup>&</sup>lt;sup>1</sup> For detailed figures by States, 1859-1935, see Minerals Yearbook, 1937, p. 1008. <sup>2</sup> Subject to revision.

Subject to revision.
 Oklahoma included with Kansas in 1905 and 1906.
 Includes Tennessee, 1883-1907.
 Figures represent 1925-42 production only; earlier years included under "Other States."
 Figures represent 1924-42 production only; earlier years included under "Other States."
 Early production in New York included with Pennsylvania.
 Includes Alaska, 1912-33; Arkansas, 1920; Michigan, 1900-19; Missouri, 1889-1911, 1913-16, 1919-23, 1932-42; New Mexico, 1913, 1919-23; Tennessee, 1916-42; Utah, 1907-11, 1920, 1924-42

## Production of crude petroleum in the United States in 1942, by districts, States, and months [Thousands of barrels]

					iousanus (	, i surrous,	1942 1							1941
District and State	Janu- ary	Febru-	March	April	Мау	June	Julý	August	Septem- ber	October	Novem- ber	Decem- ber	Total	(total)
DISTRICT														
Pennsylvania Grade. Other Appalachian Lima-Northeastern Indiana-Michigan Illinois-Southwestern Indiana Mid-Continent:	2, 377 466 1, 647 12, 121	2, 124 455 1, 408 10, 294	2, 416 517 1, 551 10, 588	2, 492 504 1, 908 9, 640	2, 403 491 1, 996 9, 667	2, 481 502 2, 016 9, 106	2, 450 507 1, 944 9, 060	2, 404 478 1, 960 9, 017	2, 387 495 1, 932 8, 485	2, 429 486 1, 981 8, 666	2, 185 587 1, 846 8, 284	2, 244 621 1, 886 8, 247	28, 392 6, 112 22, 075 113, 175	26, 808 6, 294 16, 933 139, 780
North Louisiana, Arkansas, and Mississippi	6, 939	6, 656	7, 260	7, 292	7, 259	7, 231	7, 293	7, 252	7,068	7,054	6, 680	6, 673	84, 657	66, 645
West Texas and Southeastern New Mexico East Texas. Oklahoma, Kansas, North Texas, etc Gulf Coast Rocky Mountain California Total United States	13, 198 12, 424 34, 193 21, 957 3, 453 19, 487	11, 393 10, 905 30, 139 19, 349 3, 093 18, 145	9, 620 9, 425 32, 063 18, 600 3, 606 18, 827	7, 957 6, 419 30, 193 16, 090 3, 433 19, 125 105, 053	7, 811 9, 822 31, 426 16, 281 3, 634 19, 402 110, 192	7, 846 9, 368 31, 138 15, 797 3, 585 19, 525	8, 290 8, 947 31, 984 16, 499 3, 555 21, 303	9, 583 11, 335 32, 596 19, 794 3, 530 22, 480 120, 429	8, 949 10, 826 31, 597 18, 659 3, 611 21, 792	9, 580 11, 328 33, 081 19, 683 3, 600 22, 423 120, 311	9, 192 10, 825 32, 167 18, 992 3, 515 21, 828	9, 399 11, 247 32, 785 19, 849 3, 576 23, 989 120, 519	112, 818 122, 871 383, 312 221, 550 42, 191 248, 326 1, 385, 479	132, 077 132, 486 385, 336 225, 649 39, 957 230, 263 1, 402, 228
Total United States	128, 202	113, 901	114, 475	100,000	110, 192	108, 595	111, 784	120, 428	110, 801	120, 511	110, 101	120, 519	1, 550, 478	1, 402, 226
Arkansas California 2 Colorado	2, 251 19, 487 196 11, 503 67, 650 344 10, 843 1, 618 2, 489 679 115 8, 601 1, 503 2, 77 12, 653 1, 501 49, 139 294 2, 523 6	2,072 18,145 9,772 6,687 9,552 6,687 9,550 1,383 2,601 617 117 8,077 2662 10,982 1,332 43,202 2,281 5	2, 302 18, 827 9, 986 7, 548 376 10, 127 1, 527 2, 765 671 122 2, 554 454 296 12, 424 1, 518 39, 231 2, 725 5	2, 148 19, 125 170 9, 048 7, 493 32, 205 1, 875 2, 885 660 118 2, 118 2, 118 317 11, 689 1, 582 32, 333 32, 563 66	2, 237 19, 402 200 9, 042 7, 580 8, 974 1, 968 2, 648 657 116 1, 921 1, 522 37, 12, 039 1, 522 37, 297 2, 736 5	2, 223 19, 525 180 8, 520 8, 520 8, 142 9, 141 1, 986 2, 531 696 113 2, 057 322 11, 828 1, 560 35, 306 2, 671	2, 208 21, 303 304 8, 483 579 8, 625 9, 731 1, 912 2, 469 104 2, 310 2, 474 3, 199 12, 058 1, 526 35, 306 2, 619	2, 230 22, 480 195 8, 448 571 1, 502 1, 936 2, 366 683 99 11, 760 1, 508 42, 628 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 456 297 2, 712 2,	2, 209 21, 7958 7, 958 8, 599 8, 599 9, 348 1, 904 2, 194 4, 1481 40, 576 310 2, 702 4	2, 228 22, 429 8, 136 8, 136 9, 077 346 9, 670 1, 955 2, 126 693 877 2, 461 308 11, 616 1, 502 43, 057 321 2, 668	2, 222 21, 828 7, 801 8, 833 9, 425 1, 824 1, 953 669 78 830 2, 425 280 11, 110 1, 359 41, 426 267 2, 624	2, 298 23, 989 7, 759 8, 900 8, 900 1, 866 1, 863 678 784 268 11, 127 1, 388 43, 278 2, 667 4	26, 628 248, 326 2, 220 106, 456 6, 743 97, 636 4, 472 115, 726 21, 754 28, 833 8, 074 1, 237 31, 544 5, 421 3, 543 140, 690 17, 779 483, 371 3, 574 31, 392	26, 327 230, 263 2, 150 132, 393 7, 411 83, 242 4, 762 115, 908 16, 359 15, 327 7, 526 1, 898 39, 569 5, 185 3, 510 154, 702 16, 750 505, 572 3, 433 29, 878
Total United States: 1942 1941 Daily average, 1942	128, 262 110, 446	113, 961 100, 659 4, 070	114, 473 112, 648 3, 693	105, 053 110, 550 3, 502	110, 192 116, 941 3, 555	108, 595 114, 854 3, 620	111, 782 117, 843 3, 606	120, 429 121, 159 3, 885	115, 801 119, 320 3, 860	120, 311 125, 891 3, 881	116, 101 123, 483 3, 870	120, 519 128, 434 3, 888	1, 385, 479 3, 796	1, 402, 228 3, 842

<sup>&</sup>lt;sup>1</sup> Subject to revision.

<sup>2</sup> American Petroleum Institute.

<sup>&</sup>lt;sup>8</sup> Missouri (44), Tennessee (12), Utah (4).

The relative importance of the three outstanding producing States—Texas, California, and Oklahoma—declined further, so that in 1942 they supplied only 63.0 percent of the country total compared with 63.5 percent in 1941 and 64.5 percent in 1940 (see fig. 3).

63.5 percent in 1941 and 64.5 percent in 1940 (see fig. 3).

East Texas remained the greatest producing field, despite a decline in 1942. The Wilmington (Calif.) field rose to second place and the

Tinsley (Miss.) field to third.

Percentage of total crude petroleum produced in the United States, 1933-42, by principal States

State	1933	1934	1935	1936	1937	1938	1939	1940	1941	19421
Texas California Oklahoma	44. 5 19. 0 20. 1	42. 0 19. 2 19. 9	39. 4 20. 9 18. 6	38. 9 19. 5 18. 8	39. 9 18. 6 17. 9	39. 2 20. 6 14. 4	38. 2 17. 7 12. 7	36. 4 16. 6 11. 5	36. 1 16. 4 11. 0	34. 9 17. 9 10. 2
Total, 3 States	83.6 2.8 .5 4.6 1.6	81. 1 3. 6 . 5 5. 1 1. 9	78. 9 5. 0 . 4 5. 5 2. 1	77. 2 7. 3 . 4 5. 3 2. 5	76. 4 7. 1 . 6 5. 5 3. 1	74. 2 7. 8 2. 0 5. 0 2. 9	68. 6 7. 4 7. 5 4. 8 3. 0	64. 5 7. 7 10. 9 4. 9 2. 9	63. 5 8. 3 9. 4 5. 9 2. 8	63. 0 8. 3 7. 7 7. 0 2. 3
Arkansas Michigan Pennsylvania All other	1. 3 . 9 1. 4 3. 3	1. 1 1. 2 1. 6 3. 9	1. 1 1. 5 1. 6 3. 9	. 9 1, 1 1, 6 3, 7	.9 1.3 1.5 3.6	1. 5 1. 5 1. 4 3. 7	1.7 1.8 1.4 3.8	1.9 1.5 1.3 4.1	1.1 1.9 1.2 1.2 4.7	2. 1 1. 9 1. 6 1. 3 4. 8
Total United States	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0

<sup>&</sup>lt;sup>1</sup> Subject to revision.

## Production of crude petroleum in leading fields and districts in the United States, 1941-42, and total production since discovery 1

#### [Thousands of barrels]

	1			,
Field	94.4			Total
rieid	State	1941	1942	since dis-
				covery
East Texas	Texas	100 007	100.040	
Midway-Sunset	California		120, 943	1, 850, 135
Seminole	Oklahoma	17, 468	20, 440	932, 872
Long Beach	California	23, 687	20, 408	915, 917
Oklahoma City	Oblohomo	14, 712	13, 124	660, 302
Santa Fe Springs	Oklahoma	32, 184	26, 484	573, 398
Bradford-Allegany	California Pennsylvania-New York	8, 559	7, 763	484, 938
Coalinga		17, 200	2 20, 547	476, 547
Smackover	California		19, 285	405, 338
Cushing-Shamrock	Arkansas		4,884	380, 432
Huntington Beach	Oklahoma.	3, 223	3, 069	362, 418
Solt Crook	California	10, 755	12, 108	313, 119
Salt Creek Yates district	Wyoming	5, 076	4,719	302, 930
Kettleman Hills	Texas	6, 719	7, 481	277, 372
Amounts_Fldorado district	Vonces	13, 987	13, 015	265, 214
Gray County Wilmington Salem Caddo	Kansas	5, 230	4, 700	238, 037
Wilmington	Texas	12, 506	13, 654	199, 612
Solom	California	30, 682	33, 696	173, 717
Coddo	Illinois	29, 539	14, 705	166, 998
Conroe	Louisiana Texas	3, 096	2,667	155, 523
Rodessa	1 exas	11, 747	13, 589	142, 742
Hobbs	Arkansas-Louisiana-Texas		7,684	133, 717
Fitts	New Mexico	3, 686	2, 928	100, 801
Louden	Oklahoma	4, 223	3, 050	97, 406
Eunice	Illinois	22, 918	17, 961	87, 680
Monument	New Mexico	6,658	5, 242	58, 703
Tanco Crock	W		6, 698	53,009
Tingles	Wyoming		8,023	48, 837
Tinsley	Mississippi	15, 564	27, 106	46, 708
Wasson	Texas	13, 170	9, 401	42, 549

<sup>1</sup> Oil and Gas Journal.

<sup>&</sup>lt;sup>2</sup> Bureau of Mines.

Arkansas.—Output in Arkansas in 1942 of 26,628,000 barrels was but slightly more than the 26,327,000 barrels produced in 1941. Declines in most of the fields were offset by production of 1,218,000 barrels from the new Midway field in Lafayette County, discovered in January. Twenty-nine producing wells were completed in this field, with an average initial daily production of 101 barrels per well. Eleven completions, with an average initial daily production of 155 barrels, raised the production in the Stephens field 150 percent, but the 1942 production totaled only 614,000 barrels.

There were 103 completions in 1942, with an initial daily average production of 121 barrels, compared with 95 completions in 1941,






FIGURE 3.—Production of crude petroleum in the United States, 1941-42, by States.

## Production of crude petroleum in Arkansas, 1938-42, by fields [Thousands of barrels]

Year	At- lanta	Buck- ner	Cham- pag- nolle	El Do- rado	Mag- nolia	Mc- Kamie	Ro- dessa	Schu- ler	Smack- over	Ste- phens	Ur- bana	Other fields	Total
1938 1939 1940 1941 1942	108 721 1,013 1,034	340 662 815 816 765	452 566 581 332 273	709 630 591 534 497	68 3, 639 7, 383 7, 121 6, 364	74 891 723	2, 317 1, 358 711 497 366	6, 359 6, 430 6, 547 6, 055 5, 913	6, 406 5, 945 5, 500 5, 351 4, 907	198 196 196 251 614	422 381 468 837 985	909 1, 323 1 2,188 1 2,629 1 4,187	18, 180 21, 238 25, 775 26, 327 26, 628

<sup>1</sup> Includes crude oil consumed on leases and net change in stocks held on leases for entire State.
2 Subject to revision.

California.—The urgent need for heavy crude oils to produce naval and industrial fuels prompted a comprehensive survey and planned efforts to increase the production of such oils. Success was indicated by about 45 percent more production of heavy crude at the end of the year than at the beginning. Total crude-oil production in California amounted to 248,326,000 barrels in 1942, or 18,063,000 more than in

1941; 13,459,000 barrels of this increase was in heavy crude, which

raised the total output of that type to 40,716,000 barrels.

Biggest gain was in the San Joaquin Valley district, where production totaled 105,075,000 barrels compared with 93,811,000 in 1941. The heavy-oil fields of Coalinga, Mount Poso, and Midway-Sunset were principally responsible for this gain. Coalinga's 5,099,000-barrel increase was accompanied by the completion of 43 oil wells with an average initial daily production of 645 barrels. Twenty-six wells were completed in the Mount Poso field, with an average daily initial production of 101 barrels, and the output increased from 4,117,000 barrels in 1941 to 7,566,000 in 1942. Activity in Midway-Sunset interrupted a downward trend in production from that field, with an increase from 17,461,000 barrels to 20,470,000. Sixty-two wells were drilled, with an average initial production of 74 barrels.

Production of crude petroleum in California, 1938-42, by districts and fields <sup>1</sup>
[Thousands of barrels]

District and field	1938	1939	1940	1941	1942
San Joaquin Valley:					
Belridge	5, 312	4, 781	4, 614	4, 185	2, 917
Canal	849	1,855	2,034	1,816	1,069
Coalinga	3, 898	5, 731	9,916	14, 224	19, 323
Coles Levee 2	1 12	526	2, 589	5, 717	5, 436
Edison	1, 102	838	868	1,013	1.020
Elk Hills	3, 887	3, 830	4, 427	3, 491	4, 363
Fruitvale	3, 078	2,377	2,072	2, 085	2, 312
Greeley	1.164	811	1, 475	2, 480	2, 583
Kern River	4, 590	4, 133	4, 082	4, 315	5, 707
Kettleman Hills	25, 609	19, 568	16, 730	13, 983	13, 014
Lost Hills	1, 297	1, 222	1, 405	1, 263	1, 398
McKittrick	1, 289	1, 326	1,317	1, 422	1, 791
Midway-Sunset	22, 875	18, 960	18, 397	17, 461	20, 470
Mountain View	4, 033	2, 983	2, 415	1, 910	1,602
Mount Poso	6, 235	4, 314	3, 425	4, 117	
	1, 945	2,875	3, 304		7, 566
Rio Bravo				4, 534	3, 579
Round Mountain	5, 474	3, 528	2, 691	2,815	3, 917
Ten Section	2, 473	3, 247	3, 518	5, 232	4,805
Other San Joaquin Valley	273	1, 152	2,003	1,748	2, 203
Total San Joaquin Valley	95, 395	84, 057	87, 282	93, 811	105, 075
Coastal district:					
Capitan	1,067	876	651	740	844
Elwood	2, 247	1,545	1,286	1, 166	873
Gato Ridge			l <u>-</u>		1, 217
Rincon	1, 395	1, 238	1,609	1, 542	1,010
San Miguelito	1,044	952	1,163	1,427	1, 238
Santa Maria	6 100	0.00	2,216	3, 183	2, 726
Santa Maria Valley	6, 128	6, 305	6,096	6,908	7, 550
Ventura Avenue	12, 926	12, 935	12,570	12, 892	13, 644
Ventura-Newhall	1,903	2, 317	2,866	4, 279	3, 041
Other Coastal	186	132	101	87	1,805
Total Coastal	26, 896	26, 300	28, 558	32, 224	33, 948
Los Angeles Basin:	2, 125	0.000	0.070	0.070	0.710
Brea Olinda	4, 354	2,063	2,070	2,079	3,716
Coyote		4,013	4,053	4, 466	5, 848
DominguezHuntington Beach	9,756	7, 131	7,665	8, 495	7, 932
Huntington Beach	11, 917	9, 983	9, 592	10, 743	12,096
Inglewood.	5, 337	4,605	4, 366	4, 901	6, 750
Long Beach	20, 599	17,004	16, 010	14, 697	13, 131
Montebello	4, 147	7, 455	7, 240	4,884	3, 961
Playa del Rey	2, 305	1,801	1,498	1, 319	1, 227
Richfield	3, 333	3, 134	3, 228	2,719	2,890
Rosecrans	3, 732	4, 459	4, 259	3, 434	2,722
Santa Fe Springs	12,630	10,050	9, 438	8, 552	7, 761
Seal Beach	3, 198	2,641	2, 557	2, 430	3, 027
Torrance	5, 203	6, 418	4,007	3, 210	3, 049
Wilmington	34, 168	31, 100	30, 195	30, 672	33, 657
Other Los Angeles Basin	4, 654	2, 140	1, 863	1, 627	1, 536
Total Los Angeles Basin	127, 458	113, 997	108, 041	104, 228	109, 303

<sup>&</sup>lt;sup>1</sup> American Petroleum Institute.

<sup>&</sup>lt;sup>2</sup> Includes Tupman.

Danger to marine transportation and transfer of tankers to other services have restricted production in the Coastal district, where more oil can be produced when transportation facilities are available to The production of 33,948,000 barrels from this district was 1,724,000 barrels more than in 1941. Contributing to this was 1,217,000 barrels from the long-dormant Gato Ridge field, which was brought back to production early in the year. Although 29 wells with an average initial of 586 barrels were completed in the Santa Maria Valley field, the production of 7,550,000 barrels was only 642,000 barrels more than in 1941. Output in the Ventura Avenue field was increased 752,000 barrels to 13,644,000, aided by 16 completions with an average initial of 1,151 barrels.

The Los Angeles Basin produced 109,303,000 barrels—a gain of 5,075,000 barrels. Largest rise was in the Wilmington field, where a 2,985,000-barrel increase raised the total production to 33,657,000 barrels—the second largest in the country. Thirty-eight wells with an average initial of 245 barrels were completed in Wilmington in 1942. Huntington Beach and Inglewood also made large gains in output.

Five hundred fifty-seven oil wells were completed in California in 1942 with an average intial of 358 barrels, compared with 920 wells in 1941 with an average initial of 712 barrels. Dry holes totaled 247 compared with 179 in 1941.

The Wilmington field maintained its place by a generous margin as the largest field in the State, with Midway-Sunset and Coalinga next in order. Further decline in the Kettleman Hills light-oil field

dropped it to sixth place. Colorado.—Production of 2,220,000 barrels represented a small The only fields to increase over the 2,150,000-barrel output of 1941. show material increases were Wilson Creek, which rose from 453,000 barrels in 1941 to 533,000 in 1942, and Rangely, which rose from 220,000 barrels in 1941 to 288,000 in 1942.

Ten wells were completed in Colorado during 1942 compared with Four of the completions were in Rangely and 4 in Wilson 16 in 1941.

Creek.

Production of crude petroleum in Colorado, 1938-42, by fields [Thousands of barrels]

				<u> </u>	·					
Year	Flor- ence 1	Fort Collins <sup>2</sup>	Iles	Moffat	Price	Rangely	Tow Creek	Wilson Creek	Other fields	Total
1938 1939 1940	64 62 56 55	109 116 128 118	819 724 581 547	126 112 111 116 125	185 289 326 324 272	32 36 29 220 288	56 53 52 50 46	237 453 533	21 12 3 106 3 267 3 262	1, 412 1, 404 1, 626 2, 150 2, 220

272

288

46

111

534

125

Illinois.—Further decline in Illinois production from 132,393,000 barrels in 1941 to 106,456,000 in 1942 forecasts a greater burden on Texas, Kansas, and other sources for supplying the Great Lakes and Eastern United States areas with petroleum in future. field, whose 70,734,000 barrel output in 1940 was exceeded by the East Texas field only, dropped to second place in the State in 1942, with a

Includes Canon City.
 Includes Wellington.
 Includes crude oil consumed on leases and net change in stocks held on leases for entire State.
 Subject to revision.

production of 14,705,000 barrels. This was a slump of more than 50 percent from the 29,539,000 barrels produced in 1941. The Louden field, though declining, produced 17,961,000 barrels in 1942 and wrested first place from Salem.

New oil wells completed totaled 1,107—59 percent less than the 2,730 completed in 1941. The average initial dropped to 168 barrels

compared with 277 in 1941 and 620 in 1940.

Greatest activity was in the Rural Hill Field in Hamilton County, discovered in 1941. Seventy-six wells were completed in this field, with an average initial of 189 barrels. Production from the Dale-Hoodville field in the same county decreased from 6,195,000 barrels in 1941 to 5,294,000 in 1942 following completion of 74 wells with an average initial of 236 barrels. Notwithstanding 53 completions with an average initial of 119 barrels in the New Harmony field in White County, production in that field declined from 9,939,000 barrels in 1941 to 7,224,000 in 1942.

Production of crude petroleum in Illinois, 1938-42, by fields 1
[Thousands of barrels]

Field	1938	1939	1940	1941	1942
Aden-North Ubion Benton Goyleston	305	794	1,009	700	40
Benton			1,095	895 5, 769	49
Boyleston		169	1, 306	815	5, 48 66
entrana	1 3 022 1	2, 265	10, 642	3, 564	2, 27
ISINE	421	1, 224	479	219	18
lay City	4 005	7, 694	6, 922	4, 680	2. 71
Ovington	1.00		0,022	2, 000	1, 15
Jaie .			314	2, 483	5, 29
Jungas		209	2, 341	4, 438	2, 50
Oundas Ioodville			353	3, 712	(2)
rvington			1, 120	801	47
rvington			509	1, 037	7
				5, 913	5, 14
Gensburg ouden		987	2, 709	2,002	1, 71
ouden	1,892	18, 351	26, 596	22, 918	17, 96
			26	1,691	1, 02
ow Harmony		5	1, 503	9, 939	7, 22
		1,644	2, 744	2, 507	2, 60
orth Boos		, ,	249	826	52
				785	1, 29
			2	1, 101	1, 88
				1, 570	3, 73
alem	2, 895	50, 179	70, 734	29, 539	14, 70
audoval	151	696	704	449	23
ims				12	1, 70
t. James	49	439	1, 713	1, 871	1, 47
torms		42	1, 514	1, 398	73
OHLI		835	2, 556	1, 250	85
/ oodlawn			-, 000	2, 465	2, 99
id eastern neids	3, 926	2, 738	3, 329	3, 989	4, 33
ther fields	1, 588	3, 663	5, 982	9, 293	13, 70
	22, 349	91, 934	146, 451	128, 631	106, 28

<sup>1</sup> Oil and Gas Journal.

None of the new fields discovered compared with the larger ones of 1941. The Covington pool in Wayne County, discovered in August, was the most important. Twenty-three wells were completed in this pool, with an average initial of 479 barrels and a total production of 1,159,000 barrels up to the end of the year. Oil was found in the Benoist sand of the Boulder pool in Clinton County during the first part of the year; but it was not until October, when a well was completed to the Devonian with an initial of approximately 700 barrels.

<sup>&</sup>lt;sup>2</sup> Included in Dale.

A STATE OF THE PROPERTY OF THE

that its importance was established. The 23 wells drilled in this field in 1942 had an average initial of 128 barrels. The St. Jacob pool, discovered in Madison County in May, is particularly important because it established a substantial production in the Trenton limestone, which has heretofore been considered unimportant. The 23 wells completed in this pool had an average initial of 213 barrels.

Indiana.—Despite the discovery of 12 new pools during 1942, production in Indiana declined to 6,743,000 barrels from 7,411,000 in 1941. More than half of the production came from the Griffin field.

Oil-well completions totaled 126 compared with 262 in 1941. Greatest activity was in Gibson and Posey Counties. Discovery of production in the Devonian lime in the Dodds Bridge area in Sullivan County was the most important find of the year.

Production of crude petroleum in Indiana, 1938-42, by months
[Thousands of barrels]

Year	Jan.	Feb.	Mar.	Apr.	May	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1938	68	72	75	75	80	88	90	94	90	88	85	90	995
	59	59	59	65	87	114	135	166	176	230	262	299	1, 711
	203	235	329	314	337	366	400	505	516	583	609	581	4, 978
	627	572	642	619	648	644	656	627	595	600	566	615	7, 411
	620	524	604	594	627	588	579	571	529	532	485	490	6, 743

<sup>1</sup> Subject to revision.

Kansas.—A strong demand for Kansas crude oil, brought about by the decline in Illinois and Oklahoma production, resulted in intense activity in that State in 1942. The 1941 record output was exceeded by 17 percent. Reduction in drilling (forced by Regulation M-68) was relatively less than in any of the other major producing States except California, and the relative increase in wildcat wells drilled was greater than in any other major producing State.

The production of 97,636,000 barrels was 14,394,000 higher than the 83,242,000 barrels in 1941. Oil-well completions, totaling 813, had an average initial of 693 barrels compared with 1,420 wells of 1,032 barrels average initial in 1941; 351 wildcat wells were drilled

compared with 214 in 1941.

Greatest activity was in the Peace Creek field in Reno County, where 102 wells were completed with an average initial of 827 barrels. Although output for the year totaled 1,650,000 barrels, there are indications that this field will be much more prominent in future. The Kraft-Prusa field in Barton County completed 74 wells with an average initial of 773 barrels. Fifty-two completions in the neighboring Trapp-Sellers field, with an average initial of 738 barrels, gave it the highest production of any in the State—9,726,000 barrels.

The Petroleum Administration for War certified production rate for petroleum liquids in Kansas was raised from 253,400 barrels daily in April to 300,700 for December. Scarcity of equipment makes it difficult for operators who installed small-capacity pumping units adapted to past allowables to obtain larger equipment. They are unable to produce the greater quota, but neighboring operators who have larger pumping units in the same fields are permitted to obtain a greater share of the oil because of the higher allowable.

Production of crude petroleum in Kansas, 1938-42, by counties and selected fields 1
[Thousands of barrels]

County and field	1938	1939	1940	1941	1942
Barton:					
Silica-Raymond	5, 534	F 000	F 700		
Other fields		5,000	5, 763	7, 615	9,063
Butler•	.,	3, 109	3,344	5, 087	7, 251
Eldorado	0.000		1 1 2 1 1 1		1 July 12
Other fields	3,023	2,710	2, 651	2, 597	2, 498
Cowley		2,353	2,394	2, 633	2, 202
CowleyEllis:	2,318	2, 131	2,672	2,802	3,040
					- 10 T
Bemis-Walters	2,826	2,881	3, 419	4,866	5, 847
Burnett	36	254	1.771	3, 291	4, 097
Other fields	254	332	342	477	446
Elisworth	1 1/0	1,021	1,603	2,900	3, 161
Greenwood	3,834	3, 793	3, 227	3, 238	3, 601
Harvey:		0,.00	0, 22.	0, 200	9,001
Hollow-Nikkel	773	738	511	513	346
Other fields	308	244	176	166	
McPherson:		211	1/0	100	148
Bornholdt-Welch	173	198	1 000		
Graher-Hesston	1,082	965	1,029	1, 783	1,857
Ritz Canton			947	951	950
Voshell		1, 753	1,373	1,366	1, 145
	765	574	562	586	535
Other fields	335	377	400	600	1,006
Burrton					
DUITIOIL	3, 521	3, 187	2,625	2, 539	2, 101
Other fields.	776	770	634	675	2, 205
Rice:			1.0		-,
Chase-Campbell	2, 127	2, 256	2, 338	2, 746	3, 379
Geneseo-Edwards	1,427	1, 753	1, 814	2, 694	3,716
Other fields	1,744	1,695	1, 653	1, 457	1, 255
Russell:		7,505	-, 000	1, 10.	1, 200
Hall-Gurney	613	1. 211	2, 243	3, 520	4, 057
Trapp-Sellens	4 162	4. 255	5, 481	7, 577	9, 726
Other fields	5, 081	4, 272	4, 709	4,826	
Sedgwick	1,418	1, 247			5, 758
tefford.		1, 241	1, 156	1.093	1,011
Zenith	365			1 2 121	1.2
Other fields	300	1, 294	1,838	3, 176	3, 593
lumner		1,074	1,361	2, 164	3,058
ounner Other counties		1, 494	1, 220	977	901
oner counties	4, 769	5, 188	5, 790	7, 506	8, 926
(# # B. 1947 - E. P.A. H. C. 1948 - F. A. 1947 - A. 1947 - A. 1947 - A. 1947 - A. 1947 - A. 1947 - A. 1947 - A	FO 154	FO 100	05.010		
	58, 154	58, 129	65, 046	82, 421	96, 879

<sup>1</sup> Oil and Gas Journal.

Kentucky.—Production in Kentucky continued its downward trend until near the end of 1942, the total for the year being 4,472,000 barrels compared with 4,762,000 in 1941. During the year 48 oil wells were completed compared with 233 in 1941. Production was increased materially during November and December by the development of the Smith Mills field in Henderson County, discovered in August. Production is from the McClosky lime and Cypress sand.

Production of crude petroleum in Kentucky, 1938-42, by months
[Thousands of barrels]

Year	Jan.	Feb.	Mar.	Apr.	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1938	411	406	457	432	459	487	506	553	547	526	514	523	5, 821
	536	380	437	418	494	527	503	539	423	443	472	449	5, 621
	383	422	435	438	442	405	454	449	444	464	424	428	5, 188
	424	387	414	407	403	385	418	386	391	397	356	394	4, 762
	344	335	376	356	348	355	361	337	357	346	460	497	4, 472

<sup>1</sup> Subject to revision.

THE REPORT OF THE PROPERTY OF THE PARTY OF T

Louisiana.—Production of 115,726,000 barrels in Louisiana was

slightly less than the 115,908,000-barrel output of 1941.

The output of the Gulf Coast area dropped 4,387,000 barrels from 90.917,000 barrels in 1941 to 86,530,000 in 1942. The decline was general, with little change in the relative standing of the large fields. Ville Platte maintained first place, producing 6,446,000 barrels (a gain of 327,000) as a result of 19 completions, with an average initial of 171 barrels. A smaller decline in the Golden Meadows field than in the Jennings put the former in second place.

The greatest gain—from 1,085,000 barrels in 1941 to 2,246,000 in 1942—and the greatest activity were in the Paradis field in St. Charles Parish. The 27 completions had an average initial of 417 barrels. The Chalkley field in Cameron Parish gained 860,000 barrels to 1,514,000. Sixteen completions in the Bayou Sale field in St. Mary Parish, with an average initial of 196 barrels, raised the year's pro-

duction from the field to 943,000 barrels.

Production in northern Louisiana declined generally, but gains in the Haynesville, Olla, Little Creek, and Nebo fields raised the total output to 29,196,000 barrels from 24,991,000 in 1941.

Greatest activity during 1942 was in the old Haynesville field, where production in the Pettit lime was discovered late in 1941; 120 wells were completed, with an average initial of 412 barrels, and the output

rose from 956,000 barrels in 1941 to 4,621,000 in 1942.

The Olla field proper produced approximately 4,650,000 barrels, placing it slightly ahead of Haynesville, although it should be noted that "Olla" production includes approximately 1,300,000 barrels from the Little Creek field and approximately 200,000 from the Summerville field. The increase in Olla proper was approximately 400,000 barrels and that in Little Creek approximately 900,000. wells were completed in Little Creek, with an average initial of 153 barrels, and 3 in Olla, with an average initial of 106 barrels.

An increase from 974,000 barrels in 1941 to 3,424,000 in 1942 raised the Nebo field to fourth largest in the State, following Rodessa. Nebo was the second most active field, with 52 wells completed, but the

average initial was only 44 barrels.

In 1942, 564 oil wells were completed in Louisiana with an average of 227 barrels. Of these, 286 were in the Gulf Coast area, with an average initial of 237 barrels, and 278 were in northern Louisiana, with an average initial of 216 barrels. This compares with 1,081 completions in 1941 (467 in northern Louisiana and 616 in Gulf Louisiana), with an average initial of 189 barrels.

### Production of crude petroleum in Louisiana, 1938-42, by districts and fields [Thousands of barrels]

District and field	1938	1939	1940	1941	1942 1
Gulf Coast:					
Anse la Butte	74	04	200	1 440	1 1
Barataria	7,4	24	380	1,446	2, 23
Daran Cala		17	428	989	1,08
Bayou Sale				121	94
Black Bayou	1, 285	1,048	1,007	838	89
Bosco	2.085	1,737	1,718	1,494	1, 37
Caillou Island	6, 249	4,078	2, 493	2,002	1, 51
Cameron Meadows	1, 279	782	665	810	66
Chalkley	1, 210	224	950	654	
Charenton	1.085	2, 425			1, 51
English Bayon			2,724	1,849	1,38
English Bayou	2,176	1,613	1,565	1,301	59
Eola		943	3,935	3,668	3, 31
Garden Island	828	591	1,106	1, 225	1, 25
Gibson	984	1,128	1.335	1,407	1, 32
Golden Meadows	1	739	4,074	4,814	4, 42
Grand Bay	50	496	1,168		
Grand Laka				2,022	2, 01
Grand Lake		130	1,417	1,625	1, 15
Hackberry	3, 728	3, 216	3, 312	3, 768	3, 31
- Iowa	5, 641	4, 436	3,475	3,400	2, 50
Jeanerette	2, 485	1,772	1, 203	975	670
Jennings	7, 537	8, 119	5, 505	4,991	4, 40
Lafitte	5, 862	4,745	4,602	4, 523	
Lake Barre	657				3, 750
Leeville		347	317	219	98
	1,867	1,303	1, 135	1, 597	2, 28'
New Iberia	5, 339	4, 204	3,076	2,760	1, 80
North Crowley	362	827	1,602	2,004	
Paradis		16	350	1,085	2, 246
Port Barre	612	681	810	1,025	
Quarantine Bay	261	901			968
Roanoke			1,585	2, 311	2, 107
Ge Calaid	1,339	1,076	965	851	612
St. Gabriel				554	1,345
Sulphur	1, 244	1, 381	970	921	700
Sweet Lake	307	385	532	764	641
Tepetate	1.985	2,033	1,656	1,481	1,000
University	170	1, 444	3, 496	3, 591	3, 289
Valentine	1,691	1, 127	877	512	
Venice					237
	492	515	855	1, 163	1, 294
Ville Platte	850	3, 352	4, 493	6, 119	6, 446
White Castle	593	628	806	922	907
Other Gulf Coast	7, 511	9,760	2 12, 591	2 19, 116	2 19, 339
Total Gulf Coast					
	66, 630	68, 243	79, 178	90, 917	86, 530
Vorthern:	- I				
Caddo	2,659	2,663	2,912	3,077	2, 694
Cotton Valley	3, 527	4,384	5, 189		
Haynesville				3,459	1, 953
Homer	1, 107	1,064	987	956	4, 621
Tich	952	988	1,041	1,033	1,060
Lisbon	3, 368	1,693	1,482	896	758
Nebo 3			54	974	3, 424
Olla 4			942	4,641	6, 107
Rodessa	13, 443	9,042	6,859	5, 212	4, 100
Shreveport	131	1.840			
Urania			1,555	1,011	923
Other Northern	1,003 2,388	974 2, 755	869 2 2, 516	2 2, 900	778 2 2, 778
Total Northern	28, 578	25, 403	24, 406	24, 991	29, 196
					29, 190
otal Louisiana	95, 208	93, 646	103, 584	115, 908	115, 726

Subject to revision.
 Includes crude oil consumed on leases and net change in stocks held on leases for entire district.
 Includes Hemphill, Trout Creek, and Jena.
 Includes Little Creek and Summerville.

Michigan.—Production from new fields brought the crude-oil output in 1942 to 21,754,000 barrels, which was exceeded only in the record vear 1939.

The Reed City pool in Osceola County, discovered late in 1940, was the largest field in 1942, supplying 9,102,000 barrels compared with 2,754,000 in 1941. The Evart pool, discovered in May 1942 in the same county, contributed 169,000 barrels additional. This county had the greatest activity in the State, as 66 wells were drilled in the

Reed City pool and 15 in the Evart, with an average initial of 1,942 barrels for the 81 wells.

The Headquarters pool in Roscommon County was second largest, with an output of 2,321,000 barrels compared with 315,000 in 1941, its discovery year. Sixteen wells were completed in this pool and, with 11 others in the same county, had an average initial of 1,303 barrels. Completion of 43 wells in Bay County, with an average initial of 121 barrels, increased the production to only 485,000 barrels.

In all, 293 oil wells were completed in Michigan during 1942, with an average initial of 827 barrels. The Evart pool, mentioned above, was the most prolific discovery of 1942, in terms of initial production; but the Aetna, Norwich, and Riverside fields, discovered in Missaukee County, are significant because of development of production in hitherto barren territory.

Production of crude petroleum in Michigan, 1938-42, by fields <sup>1</sup>
[Thousands of barrels]

Year	Adams	Bloom- ingdale	Buck- eye	Head- quar- ters	Porter	Red- ding	Reed City	Sher- man	Walk- er	Win- ter- field	Other fields	Total
1938	53 54 313 1, 118 1, 030	514 3, 371 1, 001 529 283	7, 385 2, 502 1, 004 665 496	315 2, 321	1, 798 1, 331 1, 234 1, 136 891	874 3, 083 3, 986 1, 749 740	2 2,754 9,102	1, 152 433 461 288 168	1 2,821 4,218 1,292 681	8 1, 101 1, 259	6, 968 9, 867 7, 526 5, 412 4, 783	18, 745 23, 462 19, 753 16, 359 21, 754

<sup>1</sup> Data from Department of Conservation, Michigan.

Mississippi.—Although production in 1942 was 28,833,000 barrels compared with 15,327,000 in 1941, the trend during the latter part of the year was downward, dropping from 96,000 barrels daily in April to 60,000 in December. Virtually all of the production was from the Tinsley field, only a small amount coming from the Pickens, Sharpsburg, and Cary fields. All of the locations in the Tinsley field have now been drilled, and there is little probability of output in Mississippi increasing unless further discoveries are made. This is reflected in the drop in completions from 219 in 1941 to 20 in 1942.

Production of crude petroleum in Mississippi, 1939-42, by months

40,000													
Year	Jan.	Feb.	Mar.	Apr.	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1939 1940 1941 1942 <sup>1</sup>	117 551 2, 489	189 603 2, 601	235 570 <b>2,</b> 708	231 770 2, 885	252 901 2, 648	317 858 <b>2,</b> 531	276 1, 425 2, 469	578 1, 598 2, 366	761 1, 694 2, 194	17 480 1, 932 2, 126	32 448 2, 240 1, 953	53 516 2, 185 1, 863	107 4, 400 15, 327 28, 833

<sup>1</sup> Subject to revision.

Montana.—An increase of 548,000 barrels raised crude-oil production in Montana to 8,074,000 barrels in 1942. Principally responsible was the Cut Bank field, where the production was 5,509,000 barrels—489,000 more than in 1941. Seventy-five wells were completed in this field, with an average initial of 150 barrels. Completion of 46 wells in the Kevin-Sunburst field, with an average initial of 47 barrels,

was reflected in an increase in production from 1,753,000 barrels in 1941 to 1,992,000 in 1942. All the other fields, of small production, declined.

There were 123 wells completed in the State, with an average initial of 109 barrels.

Production of crude petroleum in Montana, 1938-42, by fields

[Thousands of barrels]

Year	Cat Creek	Cut Bank	Dry Creek	Elk Basin	Frannie	Kevin- Sun- burst	Lake Basin	Pon- dera	Other fields	Total
1938 1939 1940 1941 1942 2	211 . 196 187 173 138	2, 809 3, 545 4, 091 5, 020 5, 509	365 319 175 170 110	8 14 16 17 16	5 26 21	1, 290 1, 576 1, 923 1, 753 1, 992	18 18 18 17 17	210 276 305 286 264	35 16 8 1 64 1 11	4, 946 5, 960 6, 728 7, 526 8, 074

<sup>&</sup>lt;sup>1</sup> Includes crude oil consumed on leases and net change in stocks held on leases for entire State.
<sup>2</sup> Subject to revision.

Nebraska.—Production in 1942 totaled 1,237,000 barrels compared with 1,898,000 in 1941. The output declined rapidly from the peak of 221,000 barrels in October 1941 to 78,000 in December 1942. The Falls City field supplied two-thirds of the total and the Barada field a little less than one-third.

Ten wells were completed in the State in 1942, seven of them in the Barada field and two in the Falls City field.

Production of crude petroleum in Nebraska, 1939-42, by months

[Thousands of barrels]

	Jan.	Feb.	Mar.	Apr.	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1939											1	1	2
1940 1941 1942 <sup>1</sup>	123 115	101 117	113 122	132 118	131 116	134 113	7 160 104	193 99	216 90	65 221 87	90 205 78	83 169 78	276 1, 898 1, 237

<sup>&</sup>lt;sup>1</sup> Subject to revision.

New Mexico.—A sharp decline brought production down to 31,544,000 barrels in 1942 compared with 39,569,000 in the peak year 1941. The decline was general, and Maljamar was the only major field producing more in 1942 than in 1941. The Monument field maintained first place, with the neighboring Eunice field second.

The greatest drilling activity was in the Square Lake pool in Eddy County, discovered early in 1942. Ninety-two wells were completed in this field, with an average initial of 179 barrels. The total output for the year was 290,000 barrels. Completions in the Maljamar field totaled 35, with an average initial of 219 barrels, and 32 wells were completed in the Jackson-Grayburg field, with an average initial of 164 barrels. Although only 9 wells each were completed in the Arrowhead and Loco Hills fields, their average initial was 393 and 372 barrels, respectively.

### Production of crude petroleum in New Mexico, 1938-42, by districts and fields 1 [Thousands of barrels]

Year	Arrow- head	Eunice	Gray- burg- Jackson	Hobbs	Loco Hills	Malja- mar and South	Monu- ment	Vacu- um	Other South- east	North- west	Total
1938 1939 1940 1941 1942 3	(2) (2) 916 1, 429 1, 195	8, 966 7, 863 6, 561 6, 658 5, 242	1, 509 1, 773 1, 627 1, 566	5, 040 4, 401 3, 785 3, 686 2, 928	377 1, 959 2, 308 1, 583	(2) 330 760 1,651 1,740	9, 451 8, 206 6, 887 6, 960 6, 698	886 3, 028 4, 738 4, 800 3, 443	11, 321 11, 651 11, 124 10, 335 8, 417	345 303 254 206 180	36, 009 37, 668 38, 757 39, 660 32, 992

New York.—Greater drilling activity further increased the output in New York to 5,421,000 barrels compared with 5,185,000 in 1941. New completions, according to the Oil Weekly, totaled 711 compared with 674 in 1941. New York was one of the four States where 1942 completions were greater than those in 1941.

### Production of crude petroleum in New York, 1938-42, by months

#### [Thousands of barrels]

Year	Jan.	Feb.	Mar.	Apr.	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1938	444	409	455	429	447	418	404	429	406	404	391	409	5, 045
	402	363	-418	406	439	435	416	441	434	448	453	443	5, 098
	458	430	438	444	439	402	425	396	383	408	379	397	4, 999
	424	372	410	436	435	422	456	438	445	465	414	468	5, 185
	453	405	454	458	455	467	474	456	459	461	425	454	5, 421

<sup>1</sup> Subject to revision.

Ohio.—The production of 3,543,000 barrels in 1942 was slightly higher than the 3,510,000 produced in 1941. Production of Pennsylvania-Grade oil increased from 1,459,000 barrels in 1941 to 1,637,000 in 1942. Greatest activity was in Perry County, where Pennsylvania-Grade oil is produced and 80 oil wells were completed; the Clayton pool was extended both northward and westward. Washington County had 28 completions and neighboring Monroe County 15. Medina County, in the central part of the State, had 24 completions. Completions for the State totaled 235.

## Production of crude petroleum in Ohio, 1938-42, by months

#### [Thousands of barrels]

Year	Jan.	Feb.	Mar.	Apr.	May	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1938	248	258	301	274	281	286	266	301	277	278	257	271	3, 298
	252	236	274	255	288	272	269	266	247	276	260	261	3, 156
	207	234	246	264	280	260	286	287	272	296	248	279	3, 159
	278	255	273	294	300	297	298	286	300	316	289	324	3, 510
	277	262	296	317	297	322	319	297	300	308	280	268	3, 543

<sup>1</sup> Subject to revision.

Oklahoma.—Production in Oklahoma declined to 140,690,000 barrels from 154,702,000 in 1941. The largest reduction was in the Oklahoma City field, which dropped to 26,484,000 barrels from

Oil and Gas Journal.
 Included under "Other Southeast."
 Subject to revision.

32,184,000 in 1941, although the field maintained first place. nole, the second largest field, dropped to 20,408,000 barrels from 23,687,000 in 1941. Production in the Hewitt field was 3,304,000 barrels and in Osage 4,716,000, representing losses of 32 percent and

23 percent.

In 1942, 544 wells were completed in the State, with an average initial of 374 barrels, compared with 1,099 wells with an average initial of 226 barrels in 1941. Greatest activity was in the Hotulke field, Pottawatomie County, where new production was discovered in 1941 in the Viola and Wilcox formations. Thirty-four wells were completed in this field, with an average initial of 256 barrels. St. Louis field in the same county, which was extended north and east in 1941, had 24 completions, with an average initial of 237 barrels. The Apache field, discovered in Caddo County in 1941, had 19 completions, with an average initial of 2,381 barrels.

Outstanding was the discovery of the Pauls Valley field in Garvin

County in April. Thirteen wells completed in this field had the unusually high average initial of 5,253 barrels, from the Wilcox and Pennsylvanian formations. The Watchorn field, discovered in Pawnee County in May, had 11 completions, with an average initial of 551 barrels from the Wilcox, and the Ardmore pool discovered in Carter County in October had 2 completions in the Springer Sand, which had

an average initial of 666, barrels.

Production of crude petroleum in Oklahoma, 1398-42, by fields 1 [Thousands of barrels]

Field	1938	1939	1940	1941	1942
Allen	2, 475	2, 289	2, 066	1 700	1.00
A Dacue	1 '	2, 200	2,000	1,780 274	1, 36
Beebe	1,017	1,005	1,828	1, 526	1,740 1,15
Billings	2, 108	2,178	2, 209	2, 276	2,06
Bristow-Slick	2, 389	2, 403	2, 213	1,951	1,77
		2,689	2, 838	3, 282	3, 356
		1,826	2, 469	3, 354	3, 21
Coyle		386	637	1, 468	1, 660
		983	769	576	752
Cromwell	1, 288	1, 175	1, 357	1, 457	2, 380
			393	2, 543	2, 776
c doming-bitatili (CA	1 2 6/6	3, 446	3, 353	3, 223	3, 069
		358	635	1, 426	548
Edmond Fish	2,030	1.675	1,488	1, 224	1.136
r isu	1 004	1,376	1, 153	1, 359	923
Fitts	16,655	9, 120	6, 246	4, 223	3, 050
16aiuion	0 401	3, 236	3, 177	3, 086	2, 827
		1, 362	1,778	4, 860	2, 827 3, 304
Keokuk Jucien	1,713	1,176	1,091	1,029	1, 012
		3, 017	2,750	2, 067	1, 012
Nowata County	4, 390	4, 348	4, 306	3, 995	3, 787
January City	1 38 706	35, 728	35, 970	32, 184	26, 484
Olympic Osage (outside Burbank-South Burbank)	1,889	1,034	739	598	490
Ramsev		6,063	5, 904	6. 131	4,716
	528	1,489	1, 377	1, 549	1, 664
Seminole field:					1,001
Bowlegs	3, 200	2,678	2, 464	0 104	
Carr City	1, 294	922	2, 404 840	2, 134	1,900
EarlsDoro	3, 751	3, 590	3, 730	791	662
Lonawa	569	656	3, 730 766	3, 757	3, 718
Little Kiver	3, 040	2.865	2, 875	1, 245	670
St. Louis-Pearson	7, 766	11, 303	9, 331	2,705	2, 333
Seminole City	2,842	2,618	2, 501	6, 997	5, 687
Seminole City Other Seminole districts	6, 390	5, 310	4, 482	2, 243 3, 815	2, 854 2, 584
Total Saminala field					2, 004
Total Seminole fieldholem-Alechem-Tatums-Tussy	28, 852	29, 942	26, 989	23, 687	20, 408
outh Rurbant	2, 249	1,699	2, 169	2,826	2, 490
outh Burbank Other fields	3, 938	3, 150	2, 927	2,780	2, 728
AMOT HORAS	32, 271	30, 331	31, 936	36, 523	34, 015
Total Oklahoma	168, 465	153, 484	150, 767	153, 257	136, 761

<sup>1</sup> Oil and Gas Journal.

Pennsylvania.—Although the crude-oil output of 17,779,000 barrels was more than a million barrels higher than in 1941, the trend was downward after midyear, despite a price increase designed to encourage development. Although production was the largest since 1937, crude-oil stocks of Pennsylvania origin declined from 2,142,000 barrels at the end of 1941 to 1,610,000 at the end of 1942.

Pennsylvania and New York suffered less from drilling restrictions than any other State; the oil-well completions in Pennsylvania, as reported by the Oil Weekly, increased from 1,722 to 1,802, although those in the Bradford field (partly in New York) declined from

1,540 to 1,493.

Production of crude petroleum in Pennsylvania, 1938-42, by months
[Thousands of barrels]

Year	Jan.	Feb.	Mar.	Apr.	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1938	1, 566 1, 346 1, 522 1, 416 1, 501	1, 255 1, 505 1, 231	1, 437 1, 530 1, 336	1, 411 1, 582 1, 382	1,558 1,585 1,407	1, 437 1, 335 1, 345	1, 405 1, 418 1, 419	1,479 1,387 1,376	1,414 1,321 1,440	1,570 1,405 1,501	1,532 1,319 1,370	1, 538 1, 444 1, 527	17, 426 17, 382 17, 353 16, 750 17, 779

<sup>1</sup> Subject to revision.

Texas.—Texas production receded 4 percent from its 1941 record of 505,572,000 barrels to 483,371,000 in 1942. Only the Panhandle area had a substantial gain, and losses in some areas were relatively large. Oil wells completed totaled 3,049 compared with 7,262 in 1941.

A slight increase brought production in the Gulf Coast area to 135,020,000 barrels. The Conroe field maintained its lead and gained 1,884,000 barrels to produce 13,514,000 in 1942. Hastings, however, had the largest gain—2,789,000 barrels—which brought its production to 10,412,000. Saxet, largest field in 1938, produced only 2,728,000 barrels in 1942.

There were 724 wells completed in the Gulf Coast area, with an average initial of 165 barrels, compared with 1,353 in 1941, with an average of 196 barrels. Greatest activity was in the Withers-Magnet field, where 62 wells were completed, with an average initial of 136 barrels, and where production increased from 2,829,000 barrels in 1941 to 4,165,000 in 1942. The Seeligson field, discovered in Jim Wells County in April 1941, had 61 completions, with an average initial of 125 barrels. There were 55 completions each in the North La Ward and Stratton fields, 38 in the Agua Dulce, and 32 in the Odem field.

The Mercy field, discovered in January 1942 in San Jacinto County, was a most important find, as it is believed to include one of the largest areas of Wilcox sand of any field in the State. There were seven completions, with an average initial of 409 barrels. Another discovery in the Wilcox sand was Camp Eleven in Tyler County, where two completions had an average initial of 594 barrels.

Production in West Texas totaled 81,775,000 barrels, compared with 92,907,000 in 1941. The Wasson field, despite a decline of 3,719,000 barrels—from 13,120,000 to 9,401,000—still ranked first. The Slaughter-Dean pool, however (with a gain of 2,732,000 barrels to 7,531,000), promises to overtake it. A 859,000-barrel gain gave

Yates 6,749,000, displacing Goldsmith, which dropped from 8,232,000

barrels to 6,569,000.

In West Texas, 1,079 oil wells were completed, with an average initial of 825 barrels, compared with 2,123 wells averaging 841 barrels in 1941. This material decline resulted from the lack of pipe-line facilities more than from the restraints on drilling from Regulation M-68 (previously described). Greatest activity was in the Slaughter field, where 421 completions had an average initial of 1,051 barrels from the San Andres lime. Wasson was the next most active field, with 93 completions and an average initial of 555 barrels; despite this, output declined 28 percent. The Keystone-Colby pool had 45 completions and the Abell pool 40, with 233 barrels and 983 barrels average initial, respectively.

Andrews County led in discoveries. Principal among the eight new fields and extensions in this county was Fullerton, discovered in February. Eight wells were completed in the field, with an average initial of 810 barrels from the Clear Fork lime. The Embar pool, discovered in this county in May, had five completions in the Ellenburger formation, with an average initial of 864 barrels. Two other wells that failed to find oil in the Ellenburger were plugged back to the Clear Fork lime and yielded an average initial of 262 barrels.

One of the most significant discoveries relating to reserves was production from the Ellenburger formation in the Monahans pool, Ward County, in May. The one well drilled had an initial of 2,852 barrels. One other well drilled to the Clear Fork lime in this pool had

an initial of 759 barrels.

Production from eastern Texas totaled 153,707,000 barrels, compared with 159,960,000 in 1941. The East Texas field proper declined 9,615,000 barrels to 122,871,000. Only five small wells were completed in this field during the year, compared with 428 in 1941. Talco had the next highest production—9,522,000 barrels—and Hawk-

ins was third at 5,451,000.

There were 240 completions in eastern Texas, with an average initial of 228 barrels, compared with 798 wells averaging 160 barrels plus 16 border wells completed in 1941. Greatest activity was in the Hawkins field, Wood County, discovered in 1940; 133 wells were completed, with an average initial of 202 barrels. Chapel Hill, in Smith County, also discovered in 1940, had 29 completions, with an

average initial of 289 barrels.

Wood County had two new discoveries in 1942 in the Paluxy sand; these were the Coke and Quitman pools. The Coke pool, found in June, had 25 completions for an average initial of 416 barrels; the Quitman pool was found on December 1, and the discovery well produced an initial of 726 barrels daily. The Kildare pool, discovered in Cass County in March, had eight completions with an average initial of 388 barrels from the Gloyd lime; and the Weiland pool, discovered in Hunt County in June, had 6 completions with an average initial of 183 barrels from the Woodbine sand.

Production in North Texas totaled 49,851,000 barrels compared with 48,529,000 in 1941. Principally responsible for the increase was development of the Ellenburger formation of the K. M. A. pool, output of which rose from 613,000 barrels in 1941 to 2,168,000 in 1942, more than offsetting the drop in yield from the shallower formations in this field. Total production for the field was 11,219,000 barrels. Of the

94 wells drilled in this field, 57 were to the Ellenburger and had an average initial of 849 barrels. The 37 other wells averaged 334 barrels. Before 1941 Ellenburger production was inconsequential in North Texas, but development in the K. M. A. field and other fields where it has since been found has added substantially to North Texas reserves.

The Hull-Silk field, with only five new completions, held second place with 3,819,000 barrels—virtually the same output as in 1941.

North Texas had 527 completions during 1942, with an average initial of 304 barrels, compared with 1,727 in 1941, with an average initial of 192 barrels. Next to K. M. A., greatest activity was in the Wimberly field in Jones County, where 29 wells were completed, with

an average initial of 331 barrels.

The Forestburg pool, discovered in May in Montague County, was one of the most important finds of the year. Seven completions in this pool had an average initial of 1,071 barrels. The Sanders pool, discovered in this same county in April, had three completions, with an average initial of 1,320 barrels. The Padgitt pool, discovered in Young County in June, had three completions, with an average initial of 1,448 barrels. Other important discoveries were the Hoefle pool in Jack County, the Cooker pool in Coleman County, and the Reddin pool in Taylor County.

Central Texas had a discovery of especial significance—the South Caesar field in Bee County, found in February. Twelve oil wells have been completed with an average initial of 338 barrels, from the Carrizo

sand.

Panhandle Texas reaped the benefit in 1942 from the 1941 drilling activity, which raised the monthly production 50 percent between the beginning and end of 1941. This area, with its increase in production from 27,831,000 barrels in 1941 to 30,881,000 in 1942, was the only one of major importance in Texas to show a substantial gain. Completions totaled 258 compared with 648 in 1941.

Production of crude petroleum in Texas, 1938-42, by districts and fields
[Thousands of barrels]

District and field	1938	1939	1940	1941	1942 1
Luis Coogts				11	
tun Coast.	1, 294	951	894	1, 220	1,375
Amelia		2,604	2, 683	4, 657	3, 589
Anahuac		3, 165	3, 180	3,076	2,879
Barbers Hill	3, 413	9, 320	9, 303	11, 630	13, 51
Conroe	11,606	9, 320	2, 940	2, 191	2 079
Dickinson-Gillock	2, 227	2,946		2, 932	2, 073 2, 78
Fairbanks	839	2, 668	2,460	2, 932	420
Flour Bluff	1,730	1, 362	1, 151	1, 336	
Friendswood	1.078	2, 323	2, 542	2, 959	3, 61 48
Goose Creek	596 1	619	571	509	
Greta		1,993	1, 493	2, 357	1, 13
Hardin		2, 180	1,646	1,659	1,09
Hastings.		6, 354	5, 421	7, 623	10, 41
Hastings		3, 470	3, 399	2,633	2, 92
Heyser High Island	900	866	966	985	88
High Island		2,077	2,005	2, 387	2, 21
Hull		1,041	957	913	80
Humble		1,041	215	1, 454	2, 26
Lolita	51	245	882	1, 334	1,78
Lovell's Lake			1, 459	1, 396	7,78
Luby	1, 578	2, 472	1, 409	1, 915	1, 90
Manvel	3, 222	2,718	2, 627	1,910	
Manvel Old Ocean	1,782	3, 209	4, 165	4,741	3, 70
Orange	483	887	889	862	6
Pierce Junction	1,117	897	628	637	56
Placedo		2, 298	1,882	1,401	1, 2
Raccoon Bend		1,034	1, 232	1, 329	1, 58

See footnotes at end of table.

Production of crude petroleum in Texas, 1938-42, by districts and fields-Continued [Thousands of barrels]

District and field	1938	1939	1940	1941	1942 1
Gulf Coast—Continued.					
Refugio	2. 093	2,097	2, 111	2, 223	1 540
Saxet-Saxet Heights	12 130	8, 953	5, 634		1, 542
Segno	700	958		4, 578	2.728
Spindleton	007		1,606	1, 538	1, 290
Sugarland	1 000	782	609	486	419
Thompsons	1, 222	1, 242	1, 354	647	614
Tomball		4,617	4, 384	4,609	5, 392
West Beaumont		2,630	2, 675	3, 314	3, 146
West Columbia	571	1,033	1, 149	821	738
West Danch	1,600	2, 261	2, 353	2,740	1,984
West Ranch	19	280	1,862	3, 691	5, 249
White Point	387	2,089	3, 054	2,864	2, 934
W ILDERS-IVI SONET	925	1,330	1,712	2,829	4, 165
Other Gulf Coast	28, 456	36, 552	2 38, 073	<sup>2</sup> 40, 256	<sup>2</sup> 40, 123
Total Gulf Coast					
	115, 587	122, 523	122, 166	134, 732	135, 020
East Texas:				*** ** ** **	37 547 74
East Texas proper 3	152, 116	144, 615	141, 023	132, 486	122,871
Cayuga	3, 191	3, 472	4, 432	4, 303	4, 419
Hawkins	0,101	0, 112	7, 704	1, 432	
Long Lake	721	867	828		5, 451
Rodessa	11 979	9, 785		1, 342	1,463
Sulphur Bluff		9, 700	6,607	4,712	3, 166
Talco	1,653	1,536	1, 522	1,582	1,549
Van		9,609	8,818	9. 038	9, 522
Other East Texas	5,630	5, 333	4, 512	3, 739	3, 444
	611	738	1, 177	1, 326	1,822
Total East Texas	184, 888	175, 955	168, 919	159, 960	153, 707
Central Texas:					
Uentral Texas: Darst Creek	0.010	0.00		1	S 10 10 4 1
Luling	2,816	2, 707	2, 178	1,845	2, 220
Lytton Springs	2, 497	2, 443	2, 256	1, 974	1,754
Morio 4	1,057	867	649	577	456
Mexia 4 Pettus	1,635	1, 494	1,418	1, 531	1,480
	2,088	1, 515	1,276	1,061	384
Salt Flat (Bruner)	1,419	1,594	1,512	1, 348	1, 118
Other Central Texas	1, 175	1,049	1, 139	1, 259	1,098
Total Central Texas	12, 687	11, 669	10, 428	9, 595	Q 510
NOTER Texas	36, 823	40, 371	6 48, 153	9, 595 48, 529	8,510
Panhandle 7	23, 556				6 49, 851
South Texas 8	29, 597	24, 165 29, 392	26, 716 32, 333	27, 831 32, 018	30, 881 23, 627
West Texas:					
Andrews County	1 200	1 50-			100
Big Lake	1,309	1,587	1,506	2, 224	1, 345
Fisher County	2, 381	2, 275	2,075	1,938	1,839
Sloraphton	1, 208	1,059	835	655	572
Slaughter	73	416	841	4,612	7, 403
Ward County	8,878	7, 795	7,580	7, 189	5, 890
Other West Texas	58, 863	66, 321	2 71, 657	<sup>2</sup> 76, 289	<sup>2</sup> 64, 726
Total West Texas	72, 712	79, 453	84, 494	92, 907	81,775
Total Texas	475, 850	483, 528	493, 209	505, 572	483, 371

West Virginia.—A small gain raised the production in West Virginia to 3,574,000 barrels compared with 3,433,000 in 1941. During the year 118 wells were completed, compared with 115 in 1941.

<sup>1</sup> Subject to revision.
2 Incldues crude oil consumed on leases and net change in stocks held on leases for entire district.
3 Joiner, Kilgore, Lathrop, and other pools in Cherokee, Gregg, Rusk, Smith, and Upshur Counties.
4 Includes other fields in Falls, Freestone, Limestone, and Navarro Counties.
5 Includes the fields in and between Wilbarger, Wichita, Clay, Montague, and Cooke Counties on the north and Runnels, Coleman, Brown, and Comanche Counties on the south.
6 Includes crude oil consumed on leases and net change in stocks held on leases for East (exclusive of East Texas proper), Central, North, and South Texas.
7 Carson, Gray, Hutchinson, Moore, Potter, and Wheeler Counties.
8 Includes fields in Duval, Hidalgo, Jim Hogg, Jim Wells, Starr, Webb, and Zapata Counties.

Production of crude petroleum in West Virginia, 1938-42, by months [Thousands of barrels]

Year	Jan.	Feb.	Mar.	Apr.	May	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1938 1939 1940 1941	290 279 234 286 294	294 282 301 249 267	337 312 285 276 310	317 288 300 300 313	322 320 311 290 297	326 309 276 280 306	304 288 303 297 306	325 310 291 283 305	315 290 286 289 310	320 309 312 311 321	257 282 264 270 267	277 311 281 302 278	3, 684 3, 580 3, 444 3, 433 3, 574

<sup>1</sup> Subject to revision.

Wyoming.—Production in Wyoming increased from 29,878,000 barrels in 1941 to 31,392,000 in 1942. Lance Creek, the principal field, decreased from 8,838,000 barrels to 7,823,000 despite the com-

pletion of 12 wells with an average initial of 171 barrels.

Although Salt Creek again declined, it maintained second place with 4,989,000 barrels output, followed closely by Oregon Basin, with a yield of 4,711,000 barrels compared with 3,197,000 in 1941. Good transportation, the need for heavy oil, and prospects for higher prices for that type of crude combined to focus attention on this field. Accordingly, 27 wells were completed, with an average initial of 451 barrels.

Ninety-three oil wells were completed in the State, with an average initial of 317 barrels, compared with 123 completions averaging 395 barrels in 1941. One of the most important finds of the year was production in November in the deep Tensleep formation of the Elk Basin field. A discovery of promising possibilities was the Horse-creek field in Laramie County in November. The one well completed in this field had an initial production of 580 barrels from the Lakota sand. New production was found in the Pilot Butte field in the Tensleep sand in March and in the Embar lime in September. The Tensleep discovery well had an initial of 750 barrels and the Embar discovery 500 barrels, which later turned to water.

Production of crude petroleum in Wyoming, 1938-42, by fields [Thousands of barrels]

			The	usands (	of darreis		<u> </u>	200		<u></u> ,
Year	Big Mud- dy	Byron- Gar- land	Cole Creek	Elk Basin	Fran- nie	Grass Creek	Hamil- ton Dome- Warm Springs	La Barge	Lance Creek	Lander- Dallas- Derby Dome
1938 1939 1940 1941 1942 1	441 435 429 421 402	836 867 1, 411 1, 516 2, 163	23 24 65 295 372	94 203 190 195 156	419 496 812 939 1,013	513 844 718 1, 171 1, 524	346 240 353 264 173	395 379 585 767 767	4, 846 6, 884 9, 121 8, 838 7, 823	306 278 290 309 294
Year	Lost Sol- dier- Ferris- Wertz	Medi- cine Bow	Oregon Basin	Osage	Poison Spider- South Casper	Quealy	Rock Creek	Salt Creek	Other fields	Total
1938	1, 037 1, 592 2, 070 4, 745 5, 118	1, 040 544 251 245 231	1, 648 1, 848 2, 725 3, 197 4, 711	116 132 59 132 114	196 26 238 251 236	271 225 172 158 170	640 1, 008 928 952 933	5, 705 5, 331 5, 201 5, 146 4, 989	150 98 293 2337 2203	19, 022 21, 454 25, 711 29, 878 31, 393

Subject to revision.
 Includes crude oil consumed on leases and net change in stocks held on leases for entire State,

#### WELLS

The number of wells drilled in the United States in 1942, including oil and gas wells and dry holes, dropped 39 percent to 17,934 compared with 29,070 in 1941.

Oil-well completions declined 46 percent—from 19,195 in 1941 to 10,302 in 1942. Regulation M-68 (previously described) was the principal reason for such severe curtailment, although exhaustion of drilling sites and lack of transportation to market for production

already acquired were contributing causes.

The greatest relative decline was in Mississippi, where exhaustion of drilling locations caused completions to drop 91 percent from 219 in 1941 to 20 in 1942. The 3,049 wells completed in Texas were 58 percent less than the 7,262 completed in 1941, and the ratio of completions to total for the United States dropped from 38 percent in 1941 to 30 in 1942. The 1,107 completions in Illinois were 59 percent less than the 2,730 in 1941, and only 11 percent of the total wells drilled in the United States were drilled in this State compared with 14 percent in 1941. The relative number of oil wells completed in the Eastern States rose from 15 percent in 1941 to 26 percent in 1942, but the actual number declined from 2,895 to 2,662, or 8 percent.




FIGURE 4.—Wells drilled in the United States, 1936-42, by months.

The 5,532 dry holes drilled in 1942 were 20 percent less than the 6,885 drilled in 1941. The smaller decline, compared with oil-well completions, reflects the lack of restrictions under Regulation M-68 against obtaining material for exploratory wells. However, difficulty in getting equipment, even with priorities, and in getting drilling crews because of lack of manpower, as well as narrowing margins of profit as drilling costs advanced against a stable crude-oil price contributed toward curtailment of exploratory operations. The Office of Price Administration proposed that the Government subsidize the cost of drilling exploratory wells to stimulate the search for new reserves yet avoid raising the price of oil. Of the total wells drilled, 3,166 were exploratory; 466 discovered oil and 57 gas, and 2,643 were dry.

The average depth per well drilled, according to the Oil Weekly, was 3,038 feet compared with 2,963 feet in 1941. Deeper drilling to

reach new production discovered in lower formations was partly offset by such factors as relatively fewer wells drilled in Illinois and Texas, where formations are deep, compared with eastern fields in which a relatively greater number of wells were drilled; and emphasis in California on heavy-oil production, the deposits of which are nearer the surface than those of light oil.

Wells drilled for oil and gas in the United States, 1941-42, by months 1

										( )			Tot	al
Wells	Jan.	Feb.	Mar.	Apr.	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Num- ber	Per- cent
1941						1 1	1 14 1	1.1						
Oil	1, 368 211 506	1, 150 198 487	1, 184 182 434	202		1, 599 220 533	1, 934 296 687	1,829 288 647		1, 821 285 644	1, 723 308 584			66. 0 10. 3 23. 7
	2, 085	1, 835	1,800	2, 417	2, 405	2, 352	2, 917	2, 764	2, 845	2, 750	2, 615	2, 285	29, 070	100.0
1942 Oil Gas Dry	1, 373 225 569	953 171 422	778 144 404	825 162 461	847 150 425	726 157 426	833 224 521	745 182 421		817 172 449	765 152 435	804 157 494	10, 302 2, 100 5, 532	57. 4 11. 7 30. 9
	2, 167	1,546	1, 326	1, 448	1, 422	1, 309	1, 578	1, 348	1, 545	1, 438	1, 352	1, 455	17, 934	100.0

<sup>&</sup>lt;sup>1</sup> Oil and Gas Journal east of California; American Petroleum Institute in California.

Wells drilled in the United States, 1941-42, by States and districts 1

State and district		19	41			19	42	<u> 1919 a</u>
State and district	Oil	Gas	Dry	Total	Oil	Gas	Dry	Total
Arkansas	95	20	83	198	103	7	74	184
California 2	920	19	179	1,118	557	25	247	829
Colorado	16	4	13	33	10	1	14	25
Illinois	2,730	12	890	3,632	1,107	14	787	1,908
Indiana	262	48	203	513	126	24	195	345
Kansas	1,420	76	517	2,013	813	79	627	1, 519
Kentucky	233	275	198	706	48	152	49	249
Louisiana:								
Gulf Coast	614	18	240	872	286	17	141	444
Northern	467	93	231	791	278	27	166	471
Total Louisiana	1,081	111	471	1,663	564	44	307	915
Michigan	433	86	419	938	293	70	300	663
Mississippi	219	4	59	282	20		48	68
Montana	160	70	53	283	123	69	26	218
Nebraska New Mexico	38	15	51 53	89 277	10 180		23 48	33 237
Oklahoma.	209	140	582		180 544	9		
Pennsylvania, New York, Ohio, and	1,099	140	582	1,821	544	92	540	1, 176
West Virginia	2,895	1.804	771	5, 470	2,662	1,306	598	4, 566
west viiginia	2, 895	1,804	. 771	5, 470	2,002	1,300	998	4, 500
Texas:								
Gulf Coast	1,353	72	387	1,812	724	67	349	1, 140
East Texas	814		14	828	240	22	145	407
West Texas	2, 123	13	163	2, 299	1,079	ĩi l	180	1, 270
Rest of State	2,972	210	1,712	4,894	1,006	102	933	2,041
m 1 m	<u>-</u>			ļ				
Total Texas	7, 262	295	2, 276	9, 833	3,049	202	1,607	4, 858
Wyoming	123	6	33	162	93	6	20	119
Other States		5	34	39			22	22
Total United States	19, 195	2,990	6, 885	29, 070	10, 302	2, 100	5, 532	17, 934

<sup>1</sup> Oil and Gas Journal, except California.

<sup>&</sup>lt;sup>2</sup> American Petroleum Institute.

Producing oil wells in the United States and average production per day in 1941, by States and districts 1

	Producin	g oil wells		Producin	g oil wells
State and district	Approxi- mate number, Dec. 31	Average produc- tion per well per day (bar- rels)	State and district	Approximate number, Dec. 31	Average produc- tion per well per day (bar- rels)
Arkansas California <sup>2</sup> Colorado. Illinois Indiana Kansas Kentucky	2, 980 16, 700 200 22, 300 1, 750 23, 200 14, 400	24. 5 39. 7 30. 2 16. 9 11. 9 10. 1 1. 9	New York Ohio Oklahoma Pennsylvania Texas: Gulf Coast	21, 500 24, 400 54, 200 81, 700	0. 7 . 4 7. 9 . 6
Louisiana: Gulf Coast Northern	2, 600 3, 900	96. 7 18. 4	East Texas proper West Texas Rest of State	25, 850 14, 300 47, 400	13. 9 19. 1 8, 6
Total Louisiana	6, 500 3, 160 330 1, 920	50. 4 14. 7 188. 7 11. 1	Total Texas West Virginia Wyoming Other States 3	100, 050 17, 400 3, 450 140	14. 2 . 5 23. 5 1. 4
Nebraska New Mexico	70 3, 610	104. 0 31. 3	Total wells	399, 960	9. 7

Figures for 1942 not yet available.
 American Petroleum Institute.
 Missouri, Tennessee, and Utah.

#### STOCKS

Total crude-oil stocks declined about 12 million barrels in 1942 compared with about 19 million barrels in 1941. An increase of over 16 million barrels in the first quarter was due to the disruption of transportation, resulting in abnormal liquidation of 27 million barrels of refined stocks that reduced the expected demand for domestic crude petroleum. While the draft on refined stocks continued during the second quarter, a sharp drop in crude production and in crude imports resulted in a decrease of about 11 million barrels in crude In spite of a substantial recovery in production, crude stocks dropped 12 million barrels more in the third quarter, mainly because of low imports of crude and efforts to rebuild stocks of refined In the fourth quarter, the seasonal rise in the demand for all oils resulted in an increased production of crude as well as a further reduction of about 5 million barrels in crude stocks. Total stocks of crude petroleum amounted to 245,219,000 barrels on December 31, 1942, compared with 257,063,000 barrels on December 31, 1942. Stocks of foreign crude declined over 2 million barrels, and stocks of domestic origin were reduced by almost 10 million barrels.

The state of the s

Stocks of crude petroleum, natural gasoline, and refined products in the United States at end of year, 1938-42

#### [Thousands of barrels]

Product	1938	1939	1940	1941	1942 1
Crude petroleum (refinable):	51, 551	49, 215	52, 448	51, 319	43, 620
At refineries Pipe line and tank farm	211, 138	178, 810	200, 726	183, 992	177, 904
Producers	11, 476	11, 953	11, 535	12, 188 11, 573	} 12, 830
Total refinable	274, 165	239, 978	264, 709	247, 499 2 246, 884	234, 354
California heavy crude	16, 467	13, 330	11, 906	10, 179	10, 865
Total crude petroleum	290, 632	253, 308	276, 615	257, 678 257, 063	} 245, 219
Natural gasoline	4,830	4, 421	5, 704	4, 275	4,632
Refined products 3	272, 241	268, 109	282,265 2 280,958	290, 375 2 294, 310	247, 554
Grand total	567, 703	525, 838	564, 584 563, 277	552, 328 2 555, 810	497, 405

The data on stocks of crude oil, by States of origin for 1942, show that the largest decreases were 12.7 million for Oklahoma, 9.0 million for Illinois, and 2.1 million for California crude of all grades. Smaller declines occurred in the stocks of all other important producing States except Texas, where stocks increased about 21.7 million barrels. These figures reflect chiefly the result of the decline in tanker movements from the Gulf to the East Coast district and the necessity of liquidating crude stocks located closer to consuming centers during the period of establishing new transport routes.

Subject to revision.
 For comparison with succeeding year.
 Includes equivalents for wax, coke, and asphalt in barrels.

## Stocks of crude petroleum in the United States in 1942, by States of location and origin and by months 1 [Thousands of barrels]

State	Jan. 1	Jan. 31	Feb. 28	Mar. 31	Apr. 30	May 31	June 30	July 31	Aug. 31	Sept. 30	Oct. 31	Nov. 30	Dec. 31
LOCATION													
Arkansas	1, 988	1.950	2,040	2, 230	2,062	1 004	1 077	1 ==0					1000
/8IIIOFIII8 * *	25 501	37, 757	39, 186	38, 548	38, 752	1,924	1,875	1,776	1,727	1,707	1, 592	1, 595	1,550
		12, 290	12, 363	11,809		37, 255	35, 672	36, 081	36, 256	34, 924	33, 025	31,744	32,770
ndiana	3,007	3, 478	3, 418		11,844	10, 923	10, 294	9,055	9, 371	9,013	9,805	9,039	9, 12
Kansas and Nebraska	9, 063	9, 464	9, 095	3,605	3,849	3, 787.	3, 558	3, 459	3, 524	2,749	2, 768	2,975	3, 19
ndiana Kansas and Nebraska Jouisiana, Alabama, and Mississippi Maryland 4	11, 739			9,091	8, 555	8, 444	8,743	9, 192	9, 199	9, 336	9, 114	9, 108	8, 39
Maryland 4	2, 149	12, 109 2, 142	11,607	11, 925	11, 493	11, 497	11, 519	10, 736	9,722	9,382	9, 439	9,643	9, 24
Maryland 4 Michigan, Kentucky, and Tennessee Missouri 6 Moreone and Colombia	3, 890		1,686	1,374	1,470	1, 267	1,437	1, 174	1,123	1, 171	1, 232	1,400	1, 26
Vissouri 6	0,890	3,669	3, 487	3, 384	3, 304	3, 316	3, 317	3, 534	3, 207	2,971	2,796	2.889	3, 06
Montana and Colorado	4, 421	4,374	4, 417	4, 103	4, 174	4,090	4,089	4, 279	4,016	4, 100	4, 263	4, 320	4, 15
Vary Targary	2, 170	2,087	1,993	1, 959	2, 104	1,966	1,874	1,893	1,727	1,522	1, 424	1, 324	1, 33
New Jersey	5, 366	4,716	3,988	3, 638	2,720	2,694	2,835	3, 153	3, 238	3, 286	2, 734	2,372	2, 62
New Mexico	1, 209	1, 280	1, 163	1, 202	1, 203	1,072	1.188	1,099	1, 188	1, 165	1,309	1, 426	1, 37
New York	1, 153	1,389	1, 338	1, 248	1, 220	1,007	1, 181	1, 150	1, 170	952	877	850	70
		9,342	9,582	9, 811	8,803	7,797	7, 352	6, 546	6, 675	6.064	5. 956	5, 759	6. 13
		38, 132	37, 891	37, 987	38, 751	38, 049	38, 550	36, 941	36, 080	35, 229	33, 257	31, 932	31, 90
		6, 145	5,776	5, 320	5, 334	5, 445	5, 829	5, 780	5, 553	5, 545	5. 217	5, 562	
		88, 870	97, 102	100, 189	97, 894	99,827	98, 230	95, 508	96, 510	97,606	99. 763		5, 50
V GSU V II E III IB	1 1 271	1, 354	1, 311	1, 355	1, 325	1, 293	1, 192	1. 122	1, 167	1.076		99, 475	99, 23
Vyoming 6	13, 317	12, 983	13, 401	13, 054	12, 904	12, 924	12, 686	12, 548	12, 672	1,070	1,053	1,027	1;07
Total United States	246, 884	253, 531	260, 844	261, 832	257, 761	254. 577	251, 421		·	12, 245	11, 737	11,660	11,70
ORIGIN	210,001	200, 001	200, 011	201, 652	201, 101	204, 077	201, 421	245, 026	244, 125	240, 043	237, 361	234, 100	234, 35
rkaneae	0							1.1					
rkansas	2,750	2,855	2, 945	3, 111	3, 020	2, 918	2,802	2,618	2, 575	2,577	2, 312	2, 276	2, 47
Zalifornia 3	35, 596	37, 767	39, 184	38, 531	38, 737	37, 249	35, 650	36,073	36, 240	34, 915	7 33, 013	31, 625	32, 75
llinois and Indiana	18, 413	18, 734	18, 958	19, 156	17, 584	14, 917	13, 656	12, 194	11, 441	10, 261	10,080	9,646	9, 49
ansas and Nebraska	7,704	8, 174	8, 126	8,086	8, 465	8, 149	8, 490	7,876	7, 274	7, 137	7, 362	7, 178	7, 05
Ouisiana and Mississippi	15, 318	16, 127	15, 697	15, 619	14, 920	15, 539	15, 759	15, 782	14, 717	14, 392	14,609	14, 543	13, 91
dichigan and Kentucky	2,943	2,608	2,571	2,601	2, 533	2, 514	2,849	2,640	2,370	2, 351	2, 209	2, 155	2, 23
Aichigan and Kentucky  Aontana and Colorado	1,865	1,806	1,677	1,655	1,869	1,693	1,594	1,549	1,422	1, 260	1, 153	1, 197	1, 12
em mexico	7.078	7, 548	7, 813	7,820	7. 188	6,715	6,058	5,720	5, 786	5.846	5, 871		
	509	517	521	489	500	516	480	505	439	487	441	5, 565	5, 80
)klahoma	51, 919	50, 964	50, 547	49,747	49, 243	47.029	45, 680	44, 184	43, 729	42,627		422	50
ennsylvania, New York, and West Virginia	3 454	3, 362	3, 270	3, 248	3, 345	3, 177	3, 215	3, 289			41, 511	39,969	39, 19
exas	00 007	86, 667	93, 161	96, 069	95, 322	99, 559	100, 760		3, 207	3,053	2,926	2,857	2,71
yoming	14 455	14, 294	14.815	14, 341	14, 195			98, 583	100,898	101, 599	102, 919	103, 662	104, 02
oreign	2, 583	2, 108	1, 559	1, 359	840	14,092	14,003	13,860	13, 794	13, 334	12,853	12,891	12,86
						510	425	153	233	204	102	114	19
Total United States		253, 531	260, 844	261, 832	257, 761	254, 577	251, 421	245, 026	244, 125	240, 043	237, 361	234, 100	234, 35
Jeavy crude in California	10, 179	10, 543	11, 229	11, 737	11, 434	11, 168	10.892	10, 950	10,706	10, 167	7 10, 868	10, 724	

Subject to revision.
 Includes Washington.
 Heavy crude stocks in California given below.

<sup>&</sup>lt;sup>4</sup> Includes Georgia, Massachusetts, Rhode Island, South Carolina, and Virginia. <sup>5</sup> Includes Iowa, Minnesota, South Dakota, and Wisconsin.

<sup>•</sup> Includes Idaho and Utah.
7744,000 barrels transferred from gasoline-bearing to heavy crude.

### Stocks of crude petroleum 1 in the United States in 1942, by districts and months 2 [Thousands of barrels]

District	Jan. 1	Jan. 31	Feb. 28	Mar. 31	Apr. 30	May 31	June 30	July 31	Aug. 31	Sept. 30	Oct. 31	Nov. 30	Dec. 31
At refineries, by field of origin:													
Appalachian:	439	448	490	466	517	437	465	670	620	511	509	491	494
Pennsylvania Grade	348	172	234	257	193	191	334	276	235	252	204	254	292
Other Appalachian (including Kentucky) Lima-Northeastern Indiana-Michigan	690	601	650	595	625	614	764	594	486	511	492	470	449
Dilinis-Southwestern Indiana. Northern Louisiana, Arkansas, and Mississippi West Texas and Southeastern New Mexico East Texas. Oklahoma, Kansas, North Texas, etc Gulf Coast	3, 423	3,622	3,632	3, 237	3, 123	2,669	2, 283	2, 140	1,986	1,976	1,921	1,959	2,043
Northern Louisiana, Arkansas, and Mississippi	3, 893	4, 251	3,773	3,834	3,867	4,040	3, 598	3, 490	2,666	2,712	3, 035	2,788	2, 969
West Texas and Southeastern New Mexico	4, 892	4, 159	3, 586	3, 450	3, 252	2,969	2.854	3, 301	3,030	2,981	3, 327	3,086	3, 244
East Texas	3,506	3,671	3,971	3, 669 11, 601	2,812 12,234	3, 350 12, 132	3, 739 11, 568	3, 593 11, 472	3, 608 11, 221	4, 290 9, 233	3, 895 9, 200	4, 343 8, 842	4, 464 9, 212
Okianoma, Kansas, North Texas, etc	10, 816 10, 344	12,055 11,883	11,824 11,466	10, 885	10, 629	10, 822	10,802	10, 463	11, 314	11, 213	10, 881	10, 975	10, 110
Pocky Mountain	2, 230	2.115	2, 202	2, 269	2, 399	2, 148	2,049	2,049	1, 828	1, 754	1, 723	1,766	1.816
California	8, 165	8, 123	8, 434	8, 428	9,034	8, 572	8, 670	8,718	9, 208	8, 932	8, 263	7,611	8, 329
Rocky Mountain California Foreign	2, 583	2, 108	1,559	1, 359	840	510	425	153	233	204	102	114	198
Total at refineries	51, 319	53, 208	51, 821	50, 050	49, 525	48, 454	47, 551	46, 919	46, 435	44, 569	43, 552	42, 699	43, 620
Pipe-line and tank-farm stocks, by fields of origin:													
Appalachian:		:_						0.40-	0.400		0.000	0.001	0.100
Pennsylvania Grade	2,880	2,748	2,605	2,596	2, 665	2, 580 1, 051	2,609 983	2, 487 1, 024	2, 438 970	2, 411 985	2, 293 948	2, 231 895	2, 132 1, 025
Pennsylvania Grade	1, 124 875	1,124 844	1,076 742	1,086 768	1,050 753	744	804	798	687	646	550	513	474
Illinois-Southwestern Indiana	14, 405	14. 517	14,726	15, 329	13,871	11.658	10, 773	9, 464	8,840	7, 680	7.549	7.057	6,814
Northern Louisiana and Arkansas	4, 968	5, 071	5, 224	5, 189	4.781	5,068	5,079	5, 264	5, 271	5, 249	4, 754	5,068	5,079
Northern Louisiana and Arkansas	19,602	21,788	24, 688	26, 486	25, 890	25, 651	26, 271	25, 524	25, 969	25, 740	25, 500	25, 704	25, 476
East Texas	16, 791	16, 905	18, 614	19,875	18, 790	20, 380	20, 505	20, 350	18, 953	19, 532	20, 789	20, 695	19,784
Oklahoma, Kansas, North Texas, etc	65,002	64, 384	65, 668	65, 945	65, 589	64, 190	65, 237	62, 522	62, 355	62, 258	62,006	59,744	59, 748
Gulf Coast	20,958	21,799	22, 782 13, 883	22, 604 13, 241	23, 544 13, 275	24, 107 13, 237	23, 054 13, 090	22, 079 12, 945	23, 335 12, 980	23,837 12,393	24, 143 11, 832	24, 953 11, 852	25, 593 11, 721
East Texas Oklahoma, Kansas, North Texas, etc	02 702	13, 594 25, 663	26, 720	26, 121	25, 729	24, 668	22, 948	23, 340	22, 959	22, 094	20, 839	19, 693	20, 058
Camornia	20, 120	20,000	20, 120	20, 121	20, 120	22,000	22,010	20,010	22,000	22,001	20,000	20,000	20,000
Total pipe line and tank farmProducers' stocks <sup>3</sup>	183, 992	188, 437	196, 728	199, 240	195, 937	193, 334	191, 353	185, 797	184, 757	182, 825	181, 203	178, 405	177, 904
Producers' stocks 8	11, 573	11,886	12, 295	12, 542	12, 299	12, 789	12, 517	12, 310	12, 933	12, 649	12, 606	12, 996	12, 830
Total United States:				*** * * * * * * * * * * * * * * * * *									1.5
Total United States: 1942	246, 884	253, 531	260, 844	261,832	257, 761	254, 577	251, 421	245, 026	244, 125	240, 043	237, 361	234, 100	234, 354
1941 4	264, 709	263, 881	265, 062	267,005	266, 637	262, 731	259, 695	255, 998	250, 240	246, 731	244, 355	244, 299	247, 499

<sup>&</sup>lt;sup>1</sup> Excludes stocks of California heavy crude.
<sup>2</sup> Subject to revision.
<sup>3</sup> Revised figures for 1941 are as follows (thousands of barrels): Producers' stocks—January 31, 11,660; February 28, 11,587; March 31, 11,786; April 30, 11,750; May 31, 11,618; June 30, 11,709; July 31, 11,809; August 31, 12,079; September 30, 12,000; October 31, 12,030; November 30, 12,617; December 31, 12,188.
<sup>4</sup> Final figures resulting from revisions indicated in footnote 3.

#### CONSUMPTION AND DISTRIBUTION

Runs to stills.—Crude runs to stills declined sharply to a total of 1,334 million barrels in 1942—a drop of 75 million barrels (5.3 percent) below the peak level of 1941. The decrease in foreign crude runs was 36 million barrels and in domestic crude runs 39 million barrels. reduction in refinery output was due to a 2-percent decline in the total demand for all oils and to a liquidation of about 47 million barrels of stocks of refined oils.

The change in refinery operations by districts varied greatly in 1942 compared with a substantial increase in all districts in 1941. Crude runs declined by about 56 million barrels in both the East Coast and Texas Gulf Coast districts, owing to the sharp curtailment in tanker movements and to the necessity of meeting demand by heavy with-drawals from stocks of refined oils in the East Coast area. The new overland movements inaugurated to supply this deficit stimulated refinery operations in the Middle West. Crude runs gained 4 million barrels in the Appalachian district and 13 million barrels in the Indiana-Illinois-Kentucky district. Crude runs in the California district rose to 230 million barrels—a gain of 17 million—owing to the increased demand by war industries, railroads, and the Navy.

Distribution.—The total demand for domestic crude petroleum fell from 1,421 million barrels in 1941 to 1,395 million barrels in 1942, or less than 2 percent. The effects of the reduction in crude runs and the liquidation of refined stocks were materially offset by the decrease of 62 million barrels in the imports of all oils, necessitating replacement of this loss in supply, at least in part, from domestic sources. All of these factors contributed to a disturbance in normal movements of crude petroleum and in the relative demand for domestic

crude petroleum by States of origin.

Receipts of domestic and foreign crude petroleum at United States refineries totaled 1,410 million barrels in 1941 and 1,328 million in 1942. In 1942 receipts of foreign crude petroleum at refineries were only about 12 million barrels, or less than 1 percent of the total compared with 3.6 percent in 1941; interstate receipts of domestic crude were 521 million barrels or 39.2 percent compared with 38.6 percent in 1941; and intrastate receipts were almost 795 million barrels or 59.8 percent compared with 57.8 percent in 1941.

Refinery receipts of crude in 1942, by methods of transportation, indicated that 80.0 percent of the total was delivered by pipe lines compared with 73.9 percent in 1941; that 9.9 percent was delivered by boat compared with 22.7 in 1941; and that 10.1 percent was delivered by tank car and truck compared with 3.4 percent in 1941. These figures indicate the sharp decline in boat movements and the

relative gain in overland shipments.

The most important changes in the market demand for crude petroleum by States of origin (computed from production and changes in crude stocks by origin) in 1942 compared with 1941 were increases of about 18 million barrels for California, 16 million for Mississippi, 14 million for Kansas, and 7 million for Michigan. The largest declines in crude demand were about 46 million barrels for Texas, 19 million for Illinois, 13 million for Oklahoma, and 7 million for New Mexico. These changes indicate shifts in production trends, in accessibility to market under disturbed transportation conditions, and in the availability of accumulated stocks.

# Runs to stills of crude petroleum in the United States in 1942, by districts and months <sup>1</sup> [Thousands of barrels]

District	January '	February	March	April	May	June	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total
East Coast: Domestic	14, 766 3, 800	12, 205 3, 417	13, 135 2, 111	10, 704 1, 317	10, 533 809	11, 121 545	12, 207 402	13, 241 212	13, 028 246	12, 635 154	12, 043 17	12, 467 27	148, 085 13, 057
Total East Coast	18, 566	15, 622	15, 246	12, 021	11,342	11, 666	12, 609	13, 453	13, 274	12, 789	12,060	12, 494	161, 142
Appalachian Indiane, Illinois, Kentucky, etc Oklahoma, Kansas, Missouri, etc Texas Inland	4, 736 21, 690 10, 830 5, 686	4, 317 20, 118 9, 588 5, 245	4, 693 21, 661 10, 080 5, 431	4, 704 20, 720 10, 715 5, 345	4, 912 22, 789 11, 142 5, 580	4, 789 21, 200 10, 575 5, 763	4, 918 23, 083 11, 352 5, 862	4, 943 22, 680 11, 300 5, 999	4, 837 22, 884 11, 025 5, 793	4, 979 23, 199 11, 084 5, 939	4, 825 21, 968 10, 929 5, 873	4, 739 22, 228 10, 762 5, 862	57, 392 264, 220 129, 382 68, 378
Texas Gulf Coast: Domestic	31, 442 210	26, 625 204	26, 117 143	24, 500 313	22, 837 367	22, 776 75	24, 344	24, 982	24, 061	25, 938 58	25, 574 33	26, 020 136	305, 216 1, 539
Total Texas Gulf Coast	31, 652	26, 829	26, 260	24, 813	23, 204	22, 851	24, 344	24, 982	24, 061	25, 996	25, 607	26, 156	306, 755
Louisiana Gulf Coast: Domestic	4, 948	4, 455	4, 685	4, 253	4, 018	4, 005	4, 582	4, 532	4, 386	4, 487	4, 387	4, 475	53, 213
Total Louisiana Gulf Coast	4, 948	4, 455	4, 685	4, 253	4, 018	4, 005	4, 582	4, 532	4, 386	4, 487	4, 387	4, 475	53, 213
Arkansas-Louisiana Inland	2, 470 3, 117 15, 337	2, 367 2, 348 14, 887	2, 361 2, 956 17, 192	2, 454 2, 647 17, 210	2, 311 2, 819 18, 766	2, 302 2, 870 19, 355	2, 398 2, 963 19, 444	2, 498 2, 916 20, 832	2, 345 3, 177 21, 692	2, 513 3, 153 22, 242	2, 289 2, 700 21, 730	2, 346 2, 803 21, 477	28, 654 34, 469 230, 164
Total domestic Total foreign	115, 022 4, 010	102, 155 3, 621	108, 311 2, 254	103, 252 1, 630	105, 707 1, 176	104, 756 620	111, 153 402	113, 923 212	113, 228 246	116, 169 212	112, 318 50	113, 179 163	1, 319, 173 14, 596
Total United States	119, 032 3, 840	105, 776 3, 778	110, 565 3, 566	104, 882 3, 496	106, 883 3, 448	105, 376 3, 513	111, 555 3, 599	114, 135 3, 682	113, 474 3, 782	116, 381 3, 754	112, 368 3, 746	113, 342 3, 656	1, 333, 769 3, 654

<sup>&</sup>lt;sup>1</sup> Subject to revision.

## Demand for crude petroleum by States of origin, 1939-42

[Thousands of barrels]

	19	39	19	40	19	41	1942 1		
State	Total	Daily ave.	Total	Daily ave.	Total	Daily ave.	Total	Daily ave.	
Arkansas	21, 491	58. 7	24, 992	68. 5	07 000	74.5	00,000		
California	228, 413		224, 931	616.3		74.5		73.	
Colorado	1, 427	3.9	1,659	4.5	232, 246 2, 050	636. 3		686.	
Illinois	89, 023	243. 2	144, 658	396.3		5.6	2. 212	6.	
Indiana	1, 596	4.4			134, 327	368.0	115, 482	316.	
Indiana Kansas	60, 733		64, 322	176. 2	7, 869	21.6	6, 638	18.	
Kentucky	5, 586		5,075		84, 209	230.7	98, 281	269.	
Louisiana	96, 650	264.1	101 105		4. 677	12.8	4,615	12.	
Michigan	23, 363		101, 185	277. 2	116, 420	319.0	116, 315	318.	
Mississippi	20, 503	2	20, 252	55. 5	15,616	42.8	22, 318	61.	
Montana	6, 227	17.0	3, 490	9.6	13, 632	37. 3	29, 646	81.	
Nebraska	0, 221	17.0		19. 1	7, 146	19.6	8,824	24.	
New Mexico	38, 954	106. 4	270	.7	1,881	5. 2	1, 244	3.	
New York	5, 352	14.6	37, 600	103.0	40,061	109.8	32, 819	89.	
			4, 908	13.4	5, 294	14.5	5, 364	14.	
Ohio Oklahoma	100 409	8.9	3, 164	8.7	3, 666	10.0	3, 552	9.	
Donnerlyonia	1 1 00 4	463.1	153, 083	419. 4	166, 357	455.8	153, 413	420.3	
Temsylvania Texas West Virginia Wyoming	17, 834	48.7	17, 481	47.9	16, 771	45.9	18, 311	50. 2	
Woot Vincinia	503, 770	1, 376. 4	480, 454	1, 316. 3	507, 283	1, 389. 8	461, 639	1, 264. 8	
Www.ing	3, 821	10.4	3, 680	10. 1	4,006	11.0	3,843	10.	
Other Cteter	24, 436	66.8	27, 525	75.4	29, 737	81.5	32, 981	90. 3	
Other States	94	.3	71	. 2	63	.1	60		
Total United States	1, 301, 580	3, 556. 2	1, 330, 323	3, 644. 7	1, 420, 517	3, 891. 8	1, 394, 938	3, 821. 7	

<sup>&</sup>lt;sup>1</sup> Subject to revision.

### Daily average demand for crude petroleum by States of origin, in 1942, by months 1 [Thousands of barrels]

State	January	February	March	April	Мау	June	July	August	Septem- ber	October	Novem- ber	Decem- ber	Year
Arkansas	69. 2	70.8	68.9	74.7	75.4	78.0	77. 2	73. 3	73. 6	80. 4	75.3	67.7	73.
California		572.9	612.0	640.8	682.4	713.3	671. 7	727.6	788. 5	762.1	778.7	732.8	686.
Colorado	7.8	6.4	5.3	4.6	6.2	7.3	5.7	7. 2	6.7	4.0	5.3	6.2	6.
Illinois		342.6	319.4	353.9	380.8	326. 2	317. 2	294.7	301.8	268.8	276.6	256.7	316.
Indiana		17.1	15.8	20.0	17.1	19.5	22. 2	20.5	20.4	16.7	14.1	14.3	18.
<u>K</u> ansas		240.6	244.7	237.0	254.8	260.1	298. 2	293. 7	291. 2	285. 5	300.2	291.1	269.
Kentucky		11.6	10.1	15.1	12.4	8.1	12.5	12.6	11.6	12.7	16.1	11.3	12
Louisiana		358.3	326.8	314.3	272.9	290.6	303. 2	359.8	319. 2	306.6	321.8	335.5	318
Michigan	56.5	51.1	50.3	61. 5	62.9	58.7	67.6	69.5	64. 4	66.1	61.8	62.4	61
Mississippi		91.0 25.5	89. 7 22. 4	112.0 15.9	82. 1 27. 1	91. 0 25. 2	89.6 24.7	83. 1 25. 2	76. 4 27. 7	66.9 28.1	59.7 21.6	47.8 24.3	81 24
Montana		4.1	4.0	4.0	3.7	3.8	3.1	3. 2	3.0	2.8	3.0	24. 3	3
Nebraska New Mexico		100.4	82. 2	88.3	77.2	90.5	85.4	85. 4	88.5	92. 9	104.5	84.1	89
New York		14.0	15. 2	13.6	14.6	15.3	13.3	13.8	17.0	15.1	14.7	15.0	14
Ohio.		9.2	10.6	10.2	9.0	11.9	9.5	11.7	8.4	11.4	10.0	6.1	9
Oklahoma		407.1	426.6	406. 4	459.8	439. 3	437. 2	394.0	416.9	410.7	421.7	383.9	420
Pennsylvania		50.1	50.4	50. 3	54.2	48.9	45. 5	52.3	51.4	51. 9	45.5	51.0	- <del>5</del> 0
Texas		1, 318. 1	1, 171. 4	1, 105, 9	1,060.8	1, 139, 3	1, 215, 1	1, 300, 4	1, 329. 2	1, 346. 4	1, 356. 6	1, 390. 9	1, 264
West Virginia		10.7	8.8	11.3	10.0	12. 2	13.3	9.7	11.7	10.7	10.4	7.1	10
Wyoming		62.9	103. 2	90.3	91.6	92.0	89.1	86.4	105. 4	101.6	86. 2	86.8	90
Other States	.2	.2	. 2	. 2	.2	.2	. 2	.2	.1	.2	.1	.1	
Total United States	3, 896. 0	3, 764. 7	3, 638. 0	3, 630. 3	3, 655. 2	3, 731. 4	3, 801. 5	3, 924. 3	4, 013. 1	3, 941. 6	3, 983. 9	3, 877. 7	3, 82

<sup>1</sup> Subject to revision.

<sup>3</sup> Missouri and Tennsessee.

The total demand for Texas crude declined from 507 million barrels in 1941 to 462 million in 1942—a loss of about 9 percent. In 1942 about 310 million barrels of Texas crude were delivered to refineries within the State—a decrease of 34 million compared with 1941. Shipments to refineries in other States amounted to about 138 million barrels or 8 million less than in 1941. Deliveries to East Coast refineries declined from 108 million barrels to 76 million but increased to the Illinois, Indiana, Kentucky, etc., district from 23 million barrels to 42 million in 1942. The sharp drop in the demand for crude petroleum resulted in an increase of almost 22 million barrels in stocks of Texas origin.

The demand for California crude increased from 232 million barrels in 1941 to over 250 million in 1942—a gain of almost 8 percent. Crude production was about 16 million barrels higher and was supplemented by a decrease of about 2 million barrels in stocks. Most of the crude was refined in the State, except for small exports to western Canada. The increase in crude demand was supplemented further by a decline

of about 9 million barrels in stocks of refined oils.

The market demand for Oklahoma crude declined from 166 million barrels in 1941 to 153 million in 1942. This decrease was due primarily to a further decline in production, as the liquidation of about 13 million barrels in stocks of origin was only 1 million barrels greater than in 1941. Deliveries to refineries within the State declined by about 4 million barrels to 52 million barrels. About 15 million barrels were delivered to refineries in Kansas and Missouri, 62 million barrels to Illinois-Indiana, Ohio, and Michigan refineries, about 15 million barrels to East Coast refineries, about 6 million to the Appalachian district, and about 7 million barrels to refineries in Texas.

The market demand for Illinois crude continued to decline as production decreased. Crude production was only about 106 million barrels in 1942—26 million less than in 1941. A decrease of 9 million barrels in stocks of Illinois origin raised crude demand to over 115 million barrels in 1942, but this amount was still 19 million barrels less than in 1941. Deliveries to refineries in Illinois amounted to 34 million barrels in 1942—a decrease of 7 million compared with 1941. Shipments to refineries in other States totaled 63 million barrels, of which 35 million went to other States in the Indiana, Illinois, Kentucky, etc., district, 19 million to the Appalachian district, and 9 million to the East Coast district. The decline in the available supply of Illinois crude contributed to the transportation problems in 1942.

The demand for Louisiana crude in 1942—116 million barrels—was virtually the same as in 1941. Deliveries to refineries within the State showed a substantial increase in 1942 to a total of about 44 million barrels, and shipments to refineries in the East Coast district increased slightly, approximating 22 million barrels. Deliveries to the Texas Gulf Coast district decreased in proportion to gains in

other districts.

The demand for Kansas crude rose to 98 million barrels in 1942. The gain of 14 million barrels, compared with 1941, approximated the increase in crude production. Deliveries to refineries in Kansas amounted to 44 million barrels; and interstate shipments increased substantially, with a total of 34 million barrels to Indiana and Illinois and about 7 million to refineries in the East Coast district.

The demand for New Mexico crude totaled 33 million barrels in 1942—a decline of 7 million compared with 1941. About 2 million barrels were delivered to refineries in the State. Shipments to the East Coast district declined about 5 million barrels and to Texas refineries about 3 million, whereas deliveries to the Illinois-Indiana

district gained 1 million barrels.

The demand for Wyoming crude increased about 3 million barrels to total 33 million in 1942. An increase in production and stock liquidation contributed to this gain in about equal proportions. Deliveries of almost 14 million barrels to refineries in the State were slightly less than in 1941. Deliveries to adjacent States in the Mountain district rose from 9 million barrels in 1941 to 10 million in 1942, and deliveries to Kansas and Indiana refineries increased over 2 million barrels.

The demand for Mississippi crude increased from almost 14 million barrels in 1941 to almost 30 million in 1942. Deliveries to Louisiana and Texas refineries declined from about 9 million barrels in 1941 to less than 5 million in 1942. Shipments to the East Coast district rose from about 1 million barrels in 1941 to 10 million in 1942; deliveries to Kentucky, Ohio, and Illinois refineries amounted to over 14 million

barrels—a gain of 9 million compared with 1941.

The demand for Arkansas crude remained virtually stationary at about 27 million barrels in 1942. Intrastate deliveries represented about half of the total demand. Shipments to Louisiana declined, but the northward movements increased substantially.

The demand for Michigan crude rose from less than 16 million barrels in 1941 to over 22 million in 1942, owing primarily to a gain in production. Over 17 million barrels were delivered to refineries in

the State; most of the balance went to Ohio refineries.

The demand for Pennsylvania crude amounted to over 18 million barrels in 1942 compared with less than 17 million in 1941. About two-thirds of the increase was due to a gain in production and the remainder to stock liquidation.

## Distribution of crude petroleum in the United States in 1942, by States <sup>1</sup> [Thousands of barrels]

State	1 1		1001	crude, by or	igm					
nsas	Production	Illinois	Kansas	Louisiana	New Mexico	Oklahoma	Texas	Other	. Runs to stills	Transfers to fuel
alifornia olorado eorgia 3	248, 326 2, 220			1				13, 410 231, 158 3, 758	13, 636 2 230, 164 3, 769 762	347 14, 670 38
linois diana ansas <sup>s</sup> entucky <sup>6</sup> uuisiana:	6,743	34, 107 2, 806 4, 440	12, 541 21, 538 43, 720	217	6, 516 258	20, 599 27, 763 10, 622	12, 841 20, 727 989	5, 090 4, 998 4, 148 12, 220	4 91, 769 77, 898 59, 933 17, 101	618 10 322 49
Gulf_ Inland aryland assachusetts <sup>1</sup> _ ichigan_	29, 196	927 1, 379 1, 732	2, 074 990	40, 027 3, 604 2, 514 4, 498	23 11	260 4, 149	8, 089 4, 539 2, 817 4, 780 3, 237	3, 981 5, 208 1, 674 1, 761 17, 358	7 53, 213 13, 159 8, 461 15, 322 27, 753	998 353 354
lssissippi issouri ontana ew Jersey	28, 833 44 8, 074	4. 093	2, 806	11, 884	843	4, 609	2, 273	1, 859 45 9, 801 12, 039	1, 859 9, 721 10, 198 58, 355	58 44 36
ew Mexico. ew York: East West	31, 544	1, 808 6, 205	410	131	2, 170	962 2, 637	3, 895 164	28 4, 665	2, 654 8, 500 14, 074	38
hio: East Westklahoma	297	12, 472 25, 833	3, 933	2, 116		770 9, 419 52, 050	4, 978 3, 404	5, 269 6, 996	18, 449 49, 699 59, 728	201 773
ennsylvania: East. West. exas:	17, 779	719 233	4, 360	<b>2</b> , 566 290	1, 611	10, 160 1, 379	43, 538 583	898 17, 566	69, 742 20, 061	Ç
Gulf	348, 351 4 3, 574	346		34, 579	19, 228 2, 672	5, 435 1, 922 1, 011	245, 503 63, 914	835 3,755 3,424	306, 755 68, 378 3, 838 4, 808	1, 360 1, 260
yoming •	31, 392	97, 100	92, 486	102. 683	33, 332	156. 866	447, 295	386, 035	14, 808 14, 010 1, 333, 769	252 21, 776

Subject to revision.
 Includes Washington.
 Includes Delaware, South Carolina, and Virginia.

<sup>4</sup> Includes Minnesota and Wisconsin.
5 Includes Nebraska and South Dakota.
6 Includes Tennessee.

<sup>Includes Alabama.
Includes Rhode Island.
Includes Idaho.</sup> 

Receipts of crude petroleum at refineries in the United States, 1938-42,1 by methods of transportation

[Millions of barrels]

Method of transportation	1938	1939	1940	1941	1942
By boat:		F0 F	70.1	69. 1	45. 2
Intrastate Interstate Foreign	74. 1 182. 8 26. 4	72. 7 188. 6 33. 1	72. 1 205. 6 42. 6	199. 9 50. 6	74. 3 12. 2
Total by boat	283. 3	294. 4	320.3	319. 6	131. 7
By pipe lines: Intrastate Interstate	600. 1 254. 3	651. 3 250. 5	671.0 268.9	728. 9 313. 1	731. 2 330. 5
Total by pipe lines	854. 4	901.8	939. 9	1, 042. 0	1, 061. 7
By tank car and truck: Intrastate Interstate	21. 9 7. 8	29. 5 10. 9	26. 1 12. 7	17. 2 31. 3	18. 0 116. 3
Total by tank car and truck	29.7	40. 4	38.8	48. 5	134.3
Grand total	1, 167. 4	1, 236. 6	1, 299. 0	1, 410. 1	1, 327. 7

<sup>&</sup>lt;sup>1</sup> Subject to revision.

#### PRICES AND VALUE

No year since 1934 has been so uneventful as 1942 in price changes for crude. The Office of Price Administration permitted only one change throughout the year in fields of major importance—an advance of 25 cents per barrel for Pennsylvania-Grade crude oil on March 26.




FIGURE 5.—Posted prices of selected grades of crude petroleum in the United States, 1934-42, by months.

Average monthly prices per barrel for selected grades of crude petroleum at wells in the United States in 1942

	Pennsylvania Grade			Okla-	Panhan- dle, Tex. (Carson			Gulf-	Cali-
Month	Brad- ford	South- west Penn- syl- vania	Illinois Basin	homa- Kansas, 36°- 36.9°	and Hutch- inson Coun- ties), 35°-35.9°	West Texas, 30°- 30.9°	East Texas	Coast Grade, 30°- 30.9°	fornia (Long Beach), 27°– 27.9°
JanuaryFebruary	\$2.75 2.75	\$2.40 2.40	\$1.37 1.37	\$1. 17 1. 17	\$1.02 1.02	\$0.92 .92	\$1.25 1.25	\$1. 28 1. 28	\$1. 15 1. 15
MarchApril	2 80 3.00 3.00	2. 45 2. 65 2. 65	1.37 1.37 1.37	1. 17 1. 17 1. 17	1. 02 1. 02 1. 02	. 92 . 92 . 92	1. 25 1. 25 1. 25	1. 28 1. 28 1. 28	1. 15 1. 15
JuneJuly	3. 00 3. 00	2. 65 2. 65	1.37 1.37	1. 17 1. 17	1.02 1.02	.92	1. 25 1. 25	1. 28 1. 28	1. 15 1. 18 1. 15
August September October	3.00 3.00 3.00	2. 65 2. 65 2. 65	1. 37 1. 37 1. 37	1. 17 1. 17 1. 17	1.02 1.02 1.02	.92 .92 .92	1. 25 1. 25 1. 25	1. 28 1. 28 1. 28	1. 15 1. 15 1. 15
November	3. 00 3. 00	2. 65 2. 65	1. 37 1. 37	1. 17 1. 17	1. 02 1. 02	. 92 . 92	1. 25 1. 25	1. 28 1. 28	1. 15 1. 15
Average for year	2.94	2. 59	1. 37	1. 17	1.02	. 92	1. 25	1. 28	1. 15

## Posted price per barrel of petroleum at wells in the United States in 1942, by grades with dates of change

	Pennsylva	nia Grade	Cornin							Oklahoma-Kansas		
Date	ate Bradford In South-		Pipe Lin	e Ke	n-	Illinois Basin 4				34°-34.9°		36°-36.9°
Jan. 1 Mar. 26	\$2.75 3.00	\$2. 40 2. 65		31 \$1	. 32	\$1.37		\$1.44		\$1.13		\$1.17
	2.94	2. 59	1.	30 1	. 32	1.	37	7 1.44		1.13		1. 17
	Panhandle Texas	Lea	Southwest				Gulf Coast					
Date	(Carson and Hutch inson Counties) 35°-35.9° 7	30°-30.9°	County,	Texas Duval Mirand 22°-22.9	[- lo,			Conroe, 30 Tex. <sup>8</sup> 30.9		200-		
Jan. 1	\$1.02	\$0.92	\$0.92	\$1.	09	\$1. 25		\$1.43	\$1.	28	\$1.0	8 \$1.18
	1.02 .92		. 92	1.09		1. 25		1.43 1		. 28 1.0		08 1.18
		Smack- over, Ark. <sup>10</sup>	Salt Creek, Wyo., 36°-36,9° 11	Lance Creek, Wyo.4	California 12							
Date	Rodessa, La., 36°- 36.9° 10				r	man, B		ong each, -27.9°	S	idway- unset, °-19.9°		Santa Fe Springs, 33°-33.9°
Jan. 1	\$1.12	\$0.83	\$1.12	\$1.12		\$1.29		\$1.15		\$0.81		\$1.26
	1.12	.83	1.12	1.12		1. 29		1.15		. 81		1.26

The Tide Water Associated Oil Co.
 The South Penn Oil Co.
 Sohio Corporation.
 The Ohio Oil Co.
 The Pure Oil Co.
 Standard Oil Co. (Indiana).

<sup>7</sup> Humble Oil & Refining Co. 8 The Texas Co. 9 Continental Oil Co. 10 Standard Oil Co. of Louisiana. 11 Standard Oil Co. of Colifornia. 12 Standard Oil Co. of California.

Value of crude petroleum at wells in the United States, 1940-41, by States 1

	19	) <del>4</del> 0	1941		
State	Total (thousands of dollars)	Average per barrel	Total (thousands of dollars)	Average per barrel	
Arkansas. California. Colorado. Illinois. Illindiana. Kansas. Kentucky.	21, 700 216, 720 1, 480 156, 500 5, 200 68, 700 5, 400	\$0.84 .97 .91 1.06 1.04 1.04	24, 500 239, 500 2, 300 172, 100 9, 400 95, 700 6, 200	\$0. 93 1. 04 1. 07 1. 30 1. 27 1. 15 1. 30	
Louisiana: Gulf CoastNorthern	83, 200 24, 300	1.05 1.00	102, 600 29, 500	1.13 1.18	
Total Louisiana. Michigan Mississippi. Montana. Nebraska New Mexico. New York Ohio. Oklahoma Pennsylvania.	3,750 6,660 220 32,500 11,600	1. 04 1. 02 . 85 . 99 . 80 . 83 2. 32 1. 30 1. 04 2. 29	132, 100 21, 900 14, 000 8, 000 1, 600 37, 200 13, 300 5, 750 174, 800 42, 500	1. 14 1. 34 . 91 1. 06 . 84 . 94 2. 57 1. 64 1. 13 2. 54	
Texas: Gulf Coast East Texas proper West Texas Rest of State	134, 500 146, 900 67, 600 145, 000	1.10 1.04 .80 1.00	167, 000 151, 000 90, 000 160, 000	1. 24 1. 14 . 97 1. 10	
Total Texas  West Virginia  Wyoming Other States 3	494, 000 6, 400 20, 600 60	1.00 1.86 .80 .85	568, 000 7, 390 25, 700 60	1.12 2.15 .86	
Total United States	1, 385, 440	1.02	1,602,000	1.14	

<sup>&</sup>lt;sup>1</sup> Figures for 1942 not yet available. <sup>2</sup> Missouri, Tennessee, and Utah.

#### REFINED PRODUCTS

#### GENERAL REVIEW

The first full year of war brought revolutionary changes in the petroleum industry. The importance of petroleum in the last war is insignificant compared with the responsibilities the industry is carrying in the present conflict. The tremendous tasks in meeting these responsibilities have brought about major alterations in the refining, transportation, and marketing of petroleum products.

War economy necessitated conversion by the refiners from a basis of producing motor fuel for automobiles as their principal output to the production of larger proportions of fuel oils, high-octane gasoline for aviation fuel, butadiene for rubber, and aromatics for toluene, cumene, and styrene; and to the construction of alcohol plants for the manufacture of rubber and explosives. The changes required entirely new sections for some refineries, whereas others had to be used with minimum changes because of scarcity of material.

Transfer of tankers to war functions threw the burden of supplying the heavily populated East Coast States on other modes of transportation—principally tank cars and pipe lines. With these facilities already insufficient to bring the full requirements to the East, the situation was aggravated by the need of shipping part of the military requirements for the North African campaign from East Coast ports.

Comparative analyses of statistics for the major refined products in the United States, 1938-42

[Thousands of barrels, except as otherwise indicated]

	1938	1939	1940	1941	1942 1
Motor fuel:					
Production Imports	569, 162	611,043	616, 695	701, 294	607, 01
Exports	50, 109	44, 638	25, 377	335 27, 083	9
Stocks, end of period.	70, 779	81, 722		f 90,688	h'
Domestic demand	523, 003	555, 509	83, 647 589, 490	2 90, 596 667, 505	586, 08
Kerosine:					= =====
Production Imports	64, 580	68, 521	73, 882	72, 586	67, 47
Exports	7, 504	8, 241	204 3, 374	191 3, 221	41
Stocks, end of period	7, 799	7, 576	9, 512	9, 599	2,72
Domestic demand	56, 360	60, 503	68, 776	2 14, 515 69, 469	10, 06 69, 61
Distillate fuel oil:		=====		00, 100	= 08,01
Production	151,774	161,746	183, 304	189, 177	196, 71
Transfers 3	623	2, 741	2,576	2, 513	2, 496
Exports	29, 641	32, 020	3, 333 19, 140	5,074	3, 42
Stocks, end of period	36, 224		\$ 42,940	16, 925 49, 926	22, 716
Domestic demand	117, 449	33, 718 134, 973	2 42, 911	2 49, 330	44, 940
Residual fuel oil:	117, 449	134, 973	160, 851	172, 824	184, 312
Production	294, 890	205 044	010 001	0.00	
	10, 037	305, 944 9, 668	316, 221 7, 699	342, 367 12, 969	358, 901 19, 283
Imports Exports	21,065	15, 680	29, 366	37, 369	17, 64
Ctooks and denoted	17, 920	17, 485	16, 109	14.114	13, 532
Stocks, end of period	101, 971	92, 290	89, 304 2 88, 026	83, 195 2 82, 959	61, 783
Domestic demand	291, 833	323, 488	340, 163	383, 422	403, 473
ubricating oil:					
Production Imports	30, 826	35, 036	36, 765	39, 539	38, 626
Exports Stocks, end of period	9, 417	11,881	11 10, 461	9, 924	8, 311
Domestic demand	7, 695 21, 233	7, 142 23, 713	8, 767 24, 690	8, 127 30, 255	9, 424
Vax (thousands of nounds).	=====	20,710	24,000	30, 200	29, 018
Production Imports Exports Stocks and of posied	435, 400	464, 520	513, 240	670 040	500 F00
Imports	28, 927	39, 913	83, 102	670, 040 16, 542	700, 560 9, 749
Stocks, end of period	201, 447	232, 664	189, 794	213, 075	153, 410
Domestic demand	129, 340 278, 532	75, 648 325, 461	125, 272 356, 924	74, 814 523, 965	85, 400 546, 313
oke (thousands of short tons):					010,010
Production	1, 602. 2	1, 666. 4	1, 526. 6	1, 648. 8	1, 338, 4
Exports Stocks, end of period	155.6	286. 2	298. 7	279.1	328. 2
Stocks, end of period Domestic demand	707. 5 1, 117. 7	666.0 1,421.7	487. 0 1, 406. 9	228. 0 1, 628. 7	233.8 1,004.4
sphalt (thousands of short tons)					1,0011
Production.	4, 341. 4	4, 954. 2	5, 346. 7	6, 557. 6	6, 296. 5
Imports Exports	33. 2 49. 9	73. 9	137. 7	158.3	142. 5
Stocks, end of period	49. 9	42. 4 550. 0	296. 4 614. 0	274. 1 604. 0	171.8 411.0
Domestic demand	4, 391. 7	4, 926. 1	5, 124. 0	6, 451. 8	6, 460. 2
oad oil:					<del></del>
Production Stocks and of posiod	7, 543	7, 868	7, 771	9, 149	8, 039
Stocks, end of period Domestic demand	680 7, 847	702 7, 846	624 7, 849	793	348
ther finished products:	-,021	1,010	1,049	8, 980	8, 484
Production	1, 921	9 920	9 000		
Exports.	1,921	2, 359 123	3, 202 708	6, 266 660	7, 795
Stocks, end of period	263	276		ſ 384	657
Domestic demand		1	359	2 489	} 597
	1,776	2, 223	2, 411	4 11, 862	4 14, 225

Subject to revision.
 New basis—to compare with following year.
 Net transfers from crude oil to fuel oil; California only, 1938.
 Includes transfers of liquefied petroleum gases from natural gasoline: 1941, 6,281,000 barrels; 1942, 7,195,000 barrels.

では 一般 ない 一般 ないとうない からない

Runs to stills and production at refineries in the United States of the various refined products, 1938-42

[Thousands of barrels, except as otherwise indicated]

Product	1938	1939	1940	1941	1942 1
Input: Crude petroleum: Domestic.	1, 138, 828	1, 204, 350	1, 252, 364	1, 358, 246	1, 319, 173
Foreign	26, 187	33, 490	41, 798	50, 946	14, 596
Total crude petroleum Natural gasoline	1, 165, 015 39, 961	1, 237, 840 39, 606	1, 294, 162 39, 547	1, 409, 192 47, 825	1, 333, 769 56, 929
Total input	1, 204, 976	1, 277, 446	1, 333, 709	1, 457, 017	1, 390, 698
Output: Gasoline Kerosine Distillate fuel oil Residual fuel oil Lubricating oil Wax. Coke Asphalt. Still gas	556, 012 64, 580 151, 774 294, 890 30, 826 1, 555 8, 011 23, 878 65, 890	596, 501 68, 521 161, 746 305, 944 35, 036 1, 659 8, 332 27, 248 68, 779	597, 375 73, 882 183, 304 316, 221 36, 765 1, 833 7, 633 29, 406 75, 950	671, 110 72, 586 189, 177 342, 367 39, 539 2, 393 8, 244 36, 067 83, 354	586, 971 67, 474 196, 714 358, 901 38, 626 2, 502 6, 692 34, 631 76, 404
Wax thousands of pounds. Coke thousands of short tons. Asphalt do Still gas millions of cubic feet.	435, 400 1, 602. 2 4, 341. 4 250, 382	464, 520 1, 666. 4 4, 954. 2 261, 360	513, 240 1, 526. 6 5, 346. 7 273, 420	670, 040 - 1, 648. 8 6, 557. 6 300, 074	700, 560 1, 338. 4 6, 296. 5 275, 054
Road oil. Other finished products Crude gasoline (net) Other unfinished oils (net) Shortage	7, 543 1, 921 2 1, 616 2 4, 530 4, 242	7, 868 2, 359 2 439 2 11, 731 5, 623	7, 771 3, 202 902 2 3, 848 3, 313	9, 149 6, 266 1, 219 2 3, 204 3 1, 250	8, 039 7, 795 1, 669 2 3, 353 7, 633
Total output	1, 204, 976	1, 277, 446	1, 333, 709	1, 457, 017	1, 390, 698

<sup>1</sup> Subject to revision.

Negative quantity; represents net excess of unfinished oils rerun over unfinished oils produced.
Negative quantity (overage).

The inadequate receipts of oil on the eastern seaboard necessitated steps to conserve the supply, including pooling of stocks and facilities of the various companies and the rationing of gasoline and heating oil. Domestic demand for motor fuel in the East Coast district during the four summer months of 1942 was cut 29 percent below that of 1941. Individual sales were of smaller gallonage, partly to permit retailers to ration their limited stocks among their customers and partly because the customers filled their tanks more frequently to avoid letting supplies get low.

Fuel-oil rationing started with a prohibition against filling home owners' tanks in the East Coast and Great Lakes areas during the summer, the usual time for replenishing the supply. This, together with an unusually cold winter and the greater number of trips necessitated because of the smaller quantity they were permitted to deliver at one time, made it difficult for retailers to deliver even the reduced

quantities permitted by the rations.

The effect of these disruptions in the industry on other economic phases of national life was shown in the loss of investment by the closing of thousands of service stations and the release of their owners and workers for other branches of the war industry; the closing of roadside restaurants, tourist camps, and similar businesses; and the drop of \$146,000,000 in State and Federal gasoline taxes, with a certainty of even less income from gasoline taxes in 1943.

Domestic demand for motor fuel dropped 12 percent—from 667 million barrels in 1941 to 586 million in 1942. An increase in exports from 27 to 36 million barrels, however, made the loss in total demand only 72 million barrels. Domestic demand for distillate fuel oil rose from 173 million to 184 million barrels and for residual fuel oil from 383 million to 403 million barrels. Exports of distillate fuel—23 million barrels—were 6 million higher than the 1941 exports, but exports of residual fuel oil declined about 1/2 million barrels.

Summary of percentage yields of refined products in the United States, 1934-42 [Computed on total crude runs to stills]

∕Product	1934	1935	1936	1937	1938	1939	1940	1941	1942 1
Finished products:									RECTAL
Gasoline: Cracked	20.4	21.5	22.4	22.6	23. 2	23.9	22.7	24. 4	22.
Straight run	23.0	22.7	21. 7	21. 3	21.1	21. 1	20.4	19.8	17.
Total gasoline	43. 4	44.2	44.1	43.9	44.3	45.0	43, 1	44.2	39.
Kerosine	6.0	5.8	5. 2	5. 5	5.5	5.5	5.7	5. 2	5.
Distillate fuel oil	10.6	10.4	11.8	12.4	13.0	13. 1	14.2	13. 4	14.
Residual fuel oil	26.8	26. 9	27.0	26.4	25.3	24.7	24.4	24.3	26.
Lubricating oil	2.9	2.9	2.9	3.0	2.6	2.8	2.8	2.8	2.
Wax	.2	. 2	.2	.2	.1	.1	. i	.2	
Coke	.7	. 7	.6	.6	.7	.7	.6	.6	
Asphalt	1.8	1.8	2.0	1,9	2.1	2. 2	2.3	2.6	2
Road oil	.7	.6	.7	.7	.6	6	.6	. 6	
Still gas	5.0	5. 3	5.3	5.4	5. 7	5. 5	5. 5	5. 9	- 5
Other	.2	.2	.2	.2	.2	.2	.3	.4	Ĭ
nfinished products:	•-	•	• • •	• •			•	•	
Gasoline	2,3	. 1	(3)	(2 3)	2.1	(2 3)	.1	.1	
Other	.2	2.3	2.8	2.7	2.4	2.9	2.3	2.2	2
hortage	1.8	1.2	.8	.5	.4	. 5	.6	2.1	
	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100

Subject to revision.
 Negative percentage: represents excess percentage rerun over percentage produced.
 Less than 0.1 percent.

Greater need for heavy oils and diminishing requirements for motor fuel forced modification in refinery operations that resulted in a drop in gasoline yield from 44.2 percent of the crude oil run to stills in 1941 to 39.7 percent in 1942. Distillate fuel-oil yields rose from 13.4 percent in 1941 to 14.7 percent in 1942 and residual fuel-oil yields from 24.3 percent to 26.9, but kerosine yields declined from 5.2 percent to 5.1.

The East Coast and Texas Gulf Coast districts were almost entirely responsible for the decline in crude-oil runs to stills. Transportation difficulties, restricting the supply of crude oil for East coast refiners

THE PARTY OF THE P

The state of the s

and depriving the Texas Gulf Coast district of its principal market for gasoline, resulted in a drop of 26 percent—from 217 million barrels in 1941 to 161 million in 1942—in the East Coast district and a drop of 16 percent—from 363 million barrels in 1941 to 307 million in 1942—in the Texas Gulf Coast district. California, with an 8-percent gain, had the greatest increase in crude runs; and the Appalachian district, with a gain of 7.3 percent, and the Indiana, Illinois, Kentucky, etc., district, with a 5.2-percent increase, followed in relative gains.

The freezing of refined-oil prices, effective November 7, 1941, was followed in 1942 by more definite regulations from the Office of Price Administration. Schedule 88, signed February 2, covered most prices except those at the service stations and provided that prices in effect




FIGURE 6.—Yields of principal petroleum products from crude oil run to stills in the United States, 1935-42, by months.

October 1, 1941, should be ceiling prices for petroleum and petroleum products. Maximum Price Regulation 137, issued April 28 and effective May 18, froze all retail prices for motor fuel and Diesel fuel at the highest March 1942 level. The General Maximum Price Regulation, also issued April 28, applied to all commodities and services not covered specifically by individual price schedules. It became effective for producer, manufacturer, and wholesaler prices on May 11, for retail prices on May 18, and for services on July 1 and likewise established the highest price charged by the individual seller during March 1942 as his maximum. As most oil prices were covered by Schedule 88 and Regulation 137, this General Regulation applied principally to services.

# Stocks of refined products in the United States, 1941-42, by months [Thousands of barrels, except as otherwise indicated]

Product	Jan. 31	Feb. 28	Mar. 31	Apr. 30	May 31	June 30	July 31	Aug. 31	Sept. 30	Oct. 31	Nov. 30	Dec. 31
Gasoline 1941 Kerosine Distillate fuel oil Residual fuel oil Lubricating oil Wax Coke Asphalt Asphalt	83, 310	88, 609	91, 501	88, 414	85, 425	82, 411	77, 429	73, 094	72, 761	74, 698	79, 378	1 86, 413
	8, 312	7, 634	6, 724	7, 063	8, 421	9, 609	10, 635	11, 636	11, 662	11, 670	10, 843	1 9, 599
	37, 926	34, 790	29, 805	31, 725	35, 389	38, 274	43, 037	47, 163	51, 412	55, 385	55, 073	1 49, 926
	85, 092	82, 902	81, 634	79, 138	79, 218	79, 948	80, 760	82, 268	83, 752	84, 960	83, 730	1 83, 195
	8, 809	8, 790	8, 637	8, 363	7, 835	7, 353	7, 107	7, 206	7, 415	7, 487	7, 752	8, 127
	429	426	435	415	423	395	362	306	284	270	272	267
	2, 030	1, 875	1, 875	2, 000	1, 925	1, 910	1, 835	1, 860	1, 850	1, 810	1, 950	1, 140
	3, 735	4, 180	4, 571	5, 132	5, 302	4, 626	3, 922	3, 328	2, 607	2, 481	2, 816	3, 322
Waxthousands of pounds. Cokethousands of short tons. Asphaltdo	120, 027	119, 150	121, 887	116, 096	118, 456	110, 481	101, 404	85, 824	79, 458	75, 467	76, 413	74, 814
	406. 0	375. 0	375. 0	400. 0	385. 0	382. 0	367. 0	372. 0	370. 0	362. 0	390. 0	228. 0
	679. 0	760. 0	831. 0	933. 0	964. 0	841. 0	713. 0	605. 0	474. 0	457. 0	512. 0	604. 0
Road oil. Other finished products. Unfinished gasoline. Other unfinished oils.	717	760	892	1, 047	1,123	1, 150	1, 028	812	658	701	690	793
	360	365	369	459	378	381	382	385	344	379	426	1 384
	7, 056	6, 949	7, 205	7, 355	7,406	7, 347	7, 272	7, 283	7, 202	7, 605	7,900	7, 685
	39, 542	39, 284	40, 227	40, 857	41,992	41, 825	41, 389	42, 005	42, 464	42, 258	40,975	39, 524
Total	277, 318	276, 564	273, 875	271, 968	274, 837	275, 229	275, 158	277, 346	282, 411	289, 704	291, 805	1 290, 375
Gasoline 1942 2 Kerosine Distillate fuel oil Residual fuel oil Lubricating oil Wax Coke Asphalt	93, 489 11, 007 40, 801 78, 386 8, 266 260 1, 229 3, 823	100, 186 9, 324 33, 711 75, 386 8, 429 270 1, 294 4, 210	99, 184 7, 900 30, 205 70, 098 8, 470 268 1, 262 4, 074	94, 127 7, 806 28, 792 67, 658 8, 470 249 1, 005 3, 957	87, 461 8, 433 30, 281 68, 388 8, 768 247 956 3, 395	80, 080 9, 497 32, 501 66, 341 8, 756 249 909 2, 826	71, 657 10, 933 37, 729 66, 935 8, 945 243 875 2, 398	71, 403 12, 176 42, 918 67, 613 9, 301 275 895 2, 181	69, 293 12, 363 45, 817 69, 264 9, 278 278 864 2, 018	67, 669 12, 645 49, 701 68, 873 9, 421 308 918 1, 887	64, 224 12, 630 50, 709 66, 664 9, 336 9,888 1,871	70, 772 10, 064 44, 940 61, 783 9, 424 305 1, 169 2, 261
W4xthousands of pounds. Cokethousands of short tons. Asphaltdo	72, 800	75, 600	75, 040	69, 720	69, 160	69, 720	68, 040	77, 000	77, 840	86, 240	86, 520	85, 400
	245. 8	258. 8	252. 4	201. 0	101. 2	181, 8	175. 0	179. 0	172. 8	183. 6	197. 6	233. 8
	695. 0	765. 4	740. 7	719. 5	617. 3	513, 8	436. 0	396. 5	366. 9	343. 1	340. 2	411. 0
Road oil. Other finished products. Unfinished gasoline. Other unfinished oils.	863	909	965	1,006	980	900	833	565	475	394	356	348
	453	503	526	556	595	552	517	502	534	537	553	597
	7, 724	8, 111	7, 549	7,695	7, 220	7, 437	7, 789	8, 123	8, 853	8, 953	8,992	9, 354
	38, 114	36, 367	36, 418	35,997	35, 319	36, 254	36, 361	36, 453	36, 747	36, 621	36,081	36, 537
Total	284, 415	278, 700	266, 919	257, 538	252, 043	246, 302	245, 215	252, 405	255, 784	257, 927	252, 713	247, 554

<sup>&</sup>lt;sup>1</sup> Stocks on new basis for January 1, 1942, are as follows: Gasoline, 86,159; kerosine, 14,515; distillate fuel oil, 49,330; residual fuel oil, 82,959; other finished products, 489; total stocks, 294,310.

Runs to stills and production at refineries in the United States of the various refined products, 1941-42, by months

[Thousands of barrels, except as otherwise indicated]

	January	February	March	April	May	June	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total
1941													
Input: Crude petroleum Natural gasoline	110, 683	100, 445	111, 059	111, 106	119, 435	115, 935	121, 180	124, 572	121, 481	126, 772	121, 539	124, 985	1, 409, 192
	3, 828	3, 312	3, 774	3, 498	3, 399	3, 518	3, 628	4, 130	4, 751	4, 997	4, 518	4, 472	47, 825
Total input	114, 511	103, 757	114, 833	114, 604	122, 834	119, 453	124, 808	128, 702	126, 232	131, 769	126, 057	129, 457	1, 457, 017
Output: Gasoline Kerosine Distillate fuel oil Residual fuel oil Lubricating oil. Wax Coke Asphalt Still gas	51, 173	46, 841	51, 950	52, 009	56, 188	55, 136	57, 714	58, 954	58, 988	61, 037	59, 480	61, 640	671, 110
	6, 661	5, 888	6, 033	6, 068	6, 033	5, 218	5, 406	5, 850	5, 949	6, 355	6, 443	6, 682	72, 586
	17, 018	14, 732	15, 387	14, 692	15, 546	14, 697	15, 746	15, 409	16, 024	16, 554	16, 230	17, 142	189, 177
	27, 880	25, 944	27, 677	26, 748	27, 994	27, 882	28, 624	29, 836	28, 118	30, 871	29, 666	31, 127	342, 367
	2, 943	2, 522	2, 813	3, 213	3, 322	3, 520	3, 563	3, 561	3, 427	3, 494	3, 607	3, 554	39, 539
	138	139	183	201	205	195	198	194	237	242	246	215	2, 393
	629	513	625	641	700	722	671	685	789	768	747	754	8, 244
	1, 667	1, 685	2, 053	2, 689	3, 310	3, 490	3, 779	4, 074	8, 741	3, 819	8, 194	2, 566	36, 067
	5, 904	5, 515	6, 806	6, 998	7, 614	7, 314	7, 531	7, 546	7, 040	7, 189	6, 825	7, 072	83, 354
Wax thousands of pounds Coke thousands of short tons Asphalt do Still gas millions of cubic feet	38, 640	38, 920	51, 240	56, 280	57, 400	54, 600	55, 440	54, 320	66, 360	67, 760	68, 880	60, 200	670, 041
	125. 8	102. 6	125. 0	128. 2	140. 0	144. 4	134. 2	137. 0	157. 8	153. 6	149. 4	150. 8	1, 648. 8
	303. 1	306. 4	373. 3	488. 9	601. 8	634. 5	687. 1	740. 7	680. 2	694. 4	580. 7	466. 5	6, 557. 6
	21, 254	19, 854	24, 502	25, 193	27, 410	26, 330	27, 112	27, 166	25, 344	25, 880	24, 570	25, 459	300, 074
Road oil. Other finished products. Unfinished gasoline (net). Other unfinished oils (net). Shortage.	218	107	198	347	846	1, 383	1,700	1, 478	1,308	793	428	343	9, 149
	452	442	548	531	580	540	556	533	506	545	545	488	6, 266
	590	1 107	256	150	51	1 59	175	11	1 81	403	295	1 215	1, 219
	1 824	1 484	567	372	780	1 551	1620	509	336	1 306	1 1, 407	1 1, 576	1 3, 204
	62	20	2 263	2 55	2 335	2 34	15	62	2 150	5	2 242	2 335	2 1, 250
Total output	114, 511	103, 757	114, 833	114, 604	122, 834	119, 453	124, 808	128, 702	126, 232	131, 769	126, 057	129, 457	1, 457, 017

See footnotes at end of table.

### Runs to stills and production at refineries in the United States of the various refined products, 1941-42, by months—Continued [Thousands of barrels, except as otherwise indicated]

	January	February	March	April	Мау	June	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total
1942 3													
Input: Crude petroleum 4 Natural gasoline	119, 032	105, 776	110, 565	104, 882	106, 883	105, 376	111, 555	114, 135	113, 474	116, 381	112, 368	113, 342	1, 333, 769
	5, 351	4, 456	<b>4, 414</b>	4, 046	4, 272	4, 423	4, 577	4, 909	5, 108	5, 455	4, 989	4, 929	56, 929
Total input	124, 383	110, 232	114, 939	108, 928	111, 155	109, 799	116, 132	119, 044	118, 582	121, 836	117, 357	118, 271	1, 390, 698
Output: Gasoline Kerosine Distillate fuel oil Residual fuel oil Lubricating oil Wax Coke Asphalt Still gas	58, 400	49, 688	50, 652	45, 889	46, 975	44, 250	47, 611	49, 488	48, 078	50, 357	48, 538	47, 045	586, 971
	6, 634	6, 133	6, 035	5, 529	5, 302	4, 929	5, 134	5, 340	5, 421	5, 907	5, 759	5, 351	67, 474
	16, 902	15, 194	16, 214	14, 002	13, 436	15, 210	16, 149	17, 052	18, 062	18, 858	17, 562	18, 073	196, 714
	29, 405	27, 254	28, 095	29, 440	30, 971	28, 352	30, 096	30, 446	30, 402	31, 239	31, 311	31, 890	358, 901
	3, 497	3, 174	3, 533	3, 438	3, 439	3, 231	3, 133	3, 141	2, 951	3, 057	2, 983	3, 049	38, 626
	197	189	220	186	185	207	181	218	204	269	214	232	2, 502
	699	606	542	457	417	438	505	554	540	615	610	709	6, 692
	2, 101	2, 105	2, 355	2, 491	2, 753	2, 848	3, 461	3, 407	3, 475	3, 613	3, 020	3,002	34, 631
	6, 609	6, 105	6, 219	6, 025	6, 306	6, 033	6, 509	6, 592	6, 146	6, 764	6, 550	6, 546	76, 404
Waxthousands of pounds_	55, 160	52, 920	61, 600	52, 080	51, 800	57, 960	50, 680	61, 040	57, 120	75, 320	59, 920	64, 960	700, 560
Cokethousands of short tons	139. 8	121. 2	108. 4	91. 4	83. 4	87. 6	101. 0	110. 8	108. 0	123. 0	122. 0	141. 8	1, 338. 4
Asphaltdo	382. 0	382. 7	428. 2	452. 9	500. 5	517. 8	629. 3	619. 5	631. 8	656. 9	549. 1	545. 8	6, 296. 5
Still gasmillions of cubic feet	23, 792	21, 978	22, 389	21, 690	22, 702	21, 719	23, 432	23, 731	22, 126	24, 350	23, 580	23, 565	275, 054
Road oil. Other finished products. Unfinished gasoline (net). Other unfinished oils (net). Shortage.	435	321	475	450	862	1, 339	1, 132	810	744	515	472	484	8, 039
	543	592	667	652	777	745	712	648	608	547	592	712	7, 795
	39	387	1 562	146	1 475	217	352	334	730	100	39	362	1, 669
	1 1, 473	1 1, 868	1 10	1 421	1 678	935	107	92	294	1 215	1 572	456	1 3, 353
	395	352	544	644	885	1, 065	1, 050	922	927	210	279	360	- 7, 633
Total output	124, 383	110, 232	114, 979	108, 928	111, 155	109, 799	116, 132	119, 044	118, 582	121, 836	117, 357	118, 271	1, 390, 698

Negative quantity; represents net excess rerun over production.
 Negative quantity (overage).
 Subject to revision.
 Detailed by districts and months in section on Consumption and Distribution of Crude Petroleum.

Runs to stills and production at refineries in the United States of the various refined products, 1941-42, by districts

[Thousands of barrels, except as otherwise indicated]

	East Coast	Appa- lachian	Indiana, Illinois, Kentucky, etc.	Oklahoma, Kansas, and Missouri	Texas Inland	Texas Gulf Coast	Louisi- ana Gulf Coast	Arkansas- Louisiana Inland	Rocky Moun- tain	Califor- nia	United States
Input:										1	
Crude petroleum Natural gasoline	217, 046 1, 984	53, 499 483	251, 257 7, 371	127, 130 4, 700	66, 640 7, 782	363, 252 9, 349	54, 300 779	29, 365 803	33, 570 789	213, 133 13, 785	1, 409, 192 47, 825
Total input	219, 030	53, 982	258, 628	131, 830	74, 422	372, 601	55, 079	30, 168	34, 359	226, 918	1, 457, 017
Output: Gasoline Kerosine Distillate fuel oil. Residual fuel oil. Lubricating oil. Wax. Coke Asphalt Still gas	11, 759 11, 720	25, 606 3, 166 4, 863 7, 709 6, 414 400 130 1, 419 2, 796	138, 481 11, 864 26, 288 46, 761 4, 307 176 4, 470 7, 303 15, 649	71, 388 7, 505 13, 431 22, 408 3, 976 160 907 2, 757 7, 702	44, 143 2, 987 2, 430 14, 280 358 5 597 1, 342 4, 698	168, 204 24, 448 59, 591 84, 806 9, 677 438 925 1, 995 26, 501	21, 265 7, 304 8, 631 13, 070 2, 093 319 2, 294 2, 357	13, 079 3, 080 2, 535 7, 180 679 1, 566 1, 224	17, 831 906 2, 778 7, 629 187 61 247 739 1, 631	85, 734 2, 157 27, 803 88, 411 3, 240 946 4, 893 9, 076	671, 110 72, 586 189, 177 342, 367 39, 539 2, 393 8, 244 36, 067 83, 354
Wax thousands of pounds.  Coke thousands of short tons.  Asphalt do  Still gas millions of cubic feet.	233, 520 4. 4 2, 138. 0 42, 192	112,000 26.0 258.0 10,065	49, 280 894. 0 1, 327. 8 56, 336	44, 800 181, 4 501, 3 27, 727	1, 400 119. 4 244. 0 16, 913	122, 640 185. 0 362. 7 95, 404	89, 320 417. 1 8, 485	284. 7 4, 406	17, 080 49. 4 134. 4 5, 872	189. 2 889. 6 32, 674	670, 040 1, 648. 8 6, 557. 6 300, 074
Road oil. Other finished products. Unfinished gasoline (net). Other unfinished oils (net). Shortage.	366 1,574 212 1 181 2 1,372	42 295 1 173 204 1,111	2, 477 1, 213 1 30 372 2 703	697 176 1 88 1 662 1, 473	146 126 1,012 2,298	173 126 618 1 1, 333 2 3, 568	3 158 99 1 <b>2</b> , 695 181	138 33 1 14 541 127	1, 651 56 1 12 100 555	3, 602 2, 489 481 1 562 2 1, 352	9, 149 6, 266 1, 219 1 3, 204 2 1, 250
Total output	219, 030	53, 982	258, 628	131, 830	74, 422	372, 601	55, 079	30, 168	34, 359	226, 918	1, 457, 017

See footnotes at end of table.

Runs to stills and production at refineries in the United States of the various refined products, 1941-42, by districts—Continued

	East Coast	Appa- lachian	Indiana, Illinois, Kentucky, etc.	Oklahoma, Kansas, and Missouri	Texas Inland	Texas Gulf Coast	Louisi- ana Gulf Coast	Arkansas- Louisiana Inland	Rocky Moun- tain	Califor- nia	United States
1942 ³											
Input: Crude petroleum Natural gasoline	161, 142 871	57, 392 511	264, 220 7, 585	129, 382 4, 096	68, 378 6, 312	306, 755 17, 799	53, 213 3, 359	28, 654 1, 379	34, 469 797	230, 164 14, 220	1, 333, 769 56, 929
Total input	162, 013	57, 903	271, 805	133, 478	74, 690	324, 554	56, 572	30, 033	35, 266	244, 384	1, 390, 698
Output: Gasoline Kerosine Distillate fuel oil Residual fuel oil Lubricating oil Wax Coke Asphalt Still gas	61, 135 7, 929 31, 132 45, 653 7, 798 763 12 4, 495 10, 425	24, 793 3, 640 6, 769 9, 498 6, 417 426 126 1, 867 2, 767	131, 347 15, 802 34, 388 55, 545 4, 326 207 4, 236 7, 273 15, 666	64, 946 8, 984 18, 344 24, 788 4, 277 207 720 2, 896 6, 002	39, 500 3, 015 3, 664 16, 586 260 12 375 2, 137 4, 208	128, 181 17, 364 60, 697 74, 778 9, 356 502 708 2, 736 23, 705	23, 182 5, 219 9, 428 11, 772 2, 066 305 81 2, 859 2, 807	11, 876 2, 460 4, 112 6, 734 1, 220 	16, 763 698 3, 782 9, 292 234 80 188 984 1, 543	85, 248 2, 363 24, 398 104, 255 2, 672 246 7, 349 8, 277	586, 971 67, 474 196, 714 358, 901 38, 626 2, 502 6, 692 34, 631 76, 404
Wax thousands of pounds.  Coke thousands of short tons.  Asphalt to compare the short tons.  Still gas millions of cubic feet.	213, 640 2. 4 817. 2 37, 531	119, 280 25, 2 339, 3 9, 961	57, 960 847. 2 1, 322. 4 56, 398	57, 960 144. 0 526. 7 21, 608	3, 360 75. 0 388. 3 15, 148	140, 560 141. 6 497. 6 85, 337	85, 400 16. 2 519. 8 10, 104	370. 1 3, 613	22, 400 37. 6 178. 9 5, 556	49. 2 1, 336. 2 29, 798	700, 560 1, 338. 4 6, 296. 5 275, 054
Road oil Other finished products. Unfinished gasoline (net). Other unfinished oils (net). Shortage	_5	30 447 32 1 15 1, 106	1, 169 1, 424 373 1 488 537	396 214 1 227 1 926 2,857	236 470 1,788 2,439	48 564 1,503 5,877 2 1,465	-1 349 1 87 1 1, 685 277	150 86 1 9 31 334	1, 363 73 8 1 140 398	4, 889 2, 616 1, 002 1 484 1, 553	8, 039 7, 795 1, 669 1 3, 353 7, 633
Total output	162, 013	57, 903	271, 805	133, 478	74, 690	324, 554	56, 572	30, 033	35, 266	244, 384	1, 390, 698

<sup>1</sup> Negative quantity; represents net excess rerun over production.

<sup>2</sup> Negative quantity (overage).

<sup>3</sup> Subject to revision.

THE RESERVE THE PROPERTY OF TH

A number of amendments have changed the ceiling prices for refined oils; the chief of them are increases to offset higher transportation costs, the rescinding of 2½ cents of the increase in gasoline prices in eastern cities when the Defense Supply Corporation assumed a like amount of the cost, and the amendment of December 26 permitting retailers to maintain a 3-cent margin between the cost and selling price of gasoline.




FIGURE 7.—Prices of Bunker "C" fuel oil at New York, bright stock at Oklahoma refineries, tank-wagon price of kerosine at Chicago, and regular-grade gasoline at refineries in Oklahoma, 1934-42, by months.

#### REFINING

Refinery capacity.—The total number of refineries dropped from 523 on January 1, 1942, to 472 on January 1, 1943, but crude-oil capacity

rose from 4.999,999 barrels daily to 5,092,411.

Cracking capacity retired in 1942 was virtually the same as that added, resulting in almost no change in completed capacity as of the beginning of 1943. Capacity in the process of construction on January 1, 1943, however, amounted to 154,984 barrels daily, which would bring the total capacity on that date to 1,347,867 barrels, compared with 1,222,684 on January 1, 1942. New processes are developing so rapidly in cracking that equipment becomes obsolete in a very short time; and it is possible that retirement of capacity will keep pace with additions, particularly in view of the declining need for gasoline and the difficulty in supplying demands for heavy oils.

The small gain in crude-oil capacity during 1942 belies the turmoil of construction throughout the country. All new refinery construction had the object of supplying war requirements, including aviation gasoline, butadiene, toluene, and alcohol, in addition to less-emphasized products. Much of the new equipment was to be used in making special commodities from certain unfinished fractions, which explains why the crude-oil capacity did not increase commensu-

rately with activity.

Government interest in the production of aviation gasoline increased rapidly during 1942. When Lease-Lend requirements began depleting stocks during the latter months of 1941 and the declaration of war shocked authorities into the realization that plant capacity must be expanded rapidly, 100-octane gasoline production became

and the second s								
Summary of	mafinama.	aama aasta.	·	1L -	TT	Class	7	4000
Summer y or	renneru	capacuu	272	tne.	i muiea	DUULES.	Jannarı T	1989_78

		Number o	f refineries		Cal	pacity (bar	rels per da	у)
Year  1939 1940	Operating 435	Shut down	Build- ing 7	Total 545 557	Operating 3, 933, 785 4, 196, 694	Shut down 574, 770 431, 952	Building	Total
1941 1942 1943	420 430 386	136 92 85	6 1 1	562 523 472	4, 180, 588 4, 496, 843 4, 404, 213	538, 381 459, 756 493, 098	92, 567 141, 225 43, 400 195, 100	4, 721, 213 4, 860, 194 4, 999, 999 5, 092, 411

one of the Nation's most important projects. Late in 1941 it was decided that 40,000 barrels per day of 100-octane gasoline were needed. After war was declared this was trebled, only to be raised in about 2 months to 180,000 barrels and soon thereafter to 250,000 barrels a day—a goal which was on the way toward accomplishment at the end of 1942, but even then was threatened with lack of material. More than 50 plants were either completed or under construction for the production of 100-octane gasoline at the end of 1942. A number of other refineries were producing the lower grades of aviation gasoline, mainly a 91-octane.

The synthetic rubber program was still handicapped by delay at the end of 1942 because of adverse weather and difficulties in obtaining priorities for critical materials. The delay in getting construction under way had prompted the appointment by the President of the Baruch Committee to investigate the rubber situation and make recommendations for expediting the program. The report of this committee, in addition to the appointment of a rubber director, led to rationing of gasoline to save tires and modified earlier plans for synthetic rubber manufacture.

Two plans were promulgated for producing rubber from petroleum—a long-range plan for permanent plants and a refinery-conversion or "quick" butadiene plan. Contracts were made in pursuance of the long-range plan for plants with a capacity of 310,000 tons annually to produce butadiene by catalytic dehydrogenation of butane and butylene in addition to 220,000 tons' capacity of plants to produce butadiene from alcohol. The first of the dehydrogenation plants, started in 1941, was completed early in 1943, and three others were completed during the immediately succeeding months. Under the second plan, 14 refineries with an annual capacity of approximately 160,000 tons had been authorized for conversion at the end of 1942, but the contracts for several of them were canceled later.

Technical developments.—During recent years technical research has taken a role of greater importance than ever before, and the discoveries and developments therefrom have changed refining from simple fractionation of petroleum to a complicated chemical industry. Wartime secrecy prevents disclosing most of the new discoveries, which include solvents, plastics, alcohol, ammonia, synthetic silks, and many others.

Developments announced during the year included moving catalysts, which foreshadow abandonment of fixed catalysts. A moving catalyst momentarily contacts the oil vapor, which travels in a parallel stream; then, the reaction completed, the two separate, and the

THE RESERVE THE PROPERTY OF THE PARTY OF THE

catalyst is regenerated away from the cracking chamber. The moving catalyst, in addition to the time saved in regeneration and the yield of a better product, presents a saving in steel that is important at this time.

Other progress during the year promises higher-octane gasoline and includes new developments in cracking and isomerization. The first oil company to receive the Army-Navy "E" was cited for its performance in producing 100-octane gasoline, toluene, and marine lubricants, particularly turbine oils.

### TRANSPORTATION

This Nation and its allies were fortunate that it had been customary to supply Atlantic coast oil needs from the Gulf coast by boat. Because of this, the second-largest and one of the best-equipped tanker fleets in the world was available for military use upon declaration of war.

Shifting a large part of these boats to military and Lend-Lease service, however, brought radical changes in the methods of transporting oil and in the social and economic life of the American people. The transfer, plus interference by submarines, resulted in tanker shipments of petroleum and its products from the Gulf area to the East coast being reduced from 430,769,000 barrels in 1941 to 123,831,000 in 1942. The daily average during the last 5 months of 1942 had dwindled to 143,000 barrels compared with 1,180,000 for 1941. The largest part of the oil requirements for the eastern United States had to be supplied by overland transportation, and a sizable proportion of the military needs was also shipped from East coast ports.

Every means available was used to move oil to the Atlantic seaboard, although economic considerations kept some facilities unavailable during the first part of 1942. Ceiling prices were too low to pay the cost of transportation in many cases, particularly on boat shipments of fuel oil from the Great Lakes area, and this kept some facilities idle that should have been in service. This defect was largely remedied later in the year; the Defense Supplies Corporation assumed the excessive carrying costs when it was deemed expedient to involve greater transportation expenses than customary without a

compensatory increase in prices.

Greatest dependence for moving oil to the East coast was placed upon the railroads. Tank-car shipments in December 1941, already increased because of difficulties in marine transportation, averaged 62,000 barrels daily. From this average they mounted to a peak of 856,710 barrels daily for 1 week in September. Tank cars were pooled, loading and unloading time was cut to the minimum, and shipments from individual refiners were grouped at assembly points from which full trains of oil cars were dispatched as express freight. Further readjustment was required and in August transportation of gasoline by tank car was prohibited in 20 of the Midwestern and Southwestern States.

Other developments and projects to aid in the distribution of oil included improvement in barge transportation, expansion and confining of tank trucks to short hauls, use of steel drums for transporting kerosine in box cars, and revamping and expanding the pipe-line

system.

Although by far the greatest dependence was put upon the railroads in 1942 for moving oil to the East coast, pipe lines did their part, and projects completed or under construction will relieve the railroads of a large part of the burden of supplying the Atlantic

seaboard with petroleum and its products.

The war concept of the pipe line is that it is merely a part of a whole, to be used as best serves the national war strategy. Changes resulting from this war concept involve much new construction and relocation, reversing, and other rearrangement of old pipe lines. Projects initiated included the laying of more than 2,300 miles of new line, taking up and relocating 1,700 miles of second-hand pipe, and converting 2,800 miles of other lines.

The most important of these changes was the construction of the "Big Inch"—the 24-inch line from east Texas to southern Illinois. It is the longest and largest pipe line ever laid for transporting oil. Oil began to move through this line in February 1943. Construction of an extension to carry the products from Illinois to the East coast

was initiated toward the end of 1942.

A 60,000-barrel feeder line was started from Houston and Port Arthur to Baton Rouge to contribute toward the supplies for the Plantation line, completed early in 1942. In addition, the terminus of the Plantation line was being extended from Greensboro, N. C., to

Rickmond, Va.

Other projects started or planned during 1942 include a 35,000-barrel-daily products line across Florida, a 15,000-barrel-daily line across Ohio, and the Sinclair line from Steubenville, Ohio, across Pennsylvania. Pipe-line completions during 1942 include reversal and conversion of the Keystone line across Pennsylvania, reversal of the Sun-Susquehanna line from Cleveland to the eastern seaboard, enlargement of the Shell line from Wood River, Ill., to Lima, Ohio, enlargement of the Texas-Empire line between Tulsa and Chicago, and reversal and conversion of a Texas Co. pipe line between Port Arthur and Dallas, Tex. The 24- to 26-inch Stanpac natural-gas pipe line, extending from Kettleman Hills to San Francisco, has been converted to crude-oil service, with a capacity of 100,000 barrels daily.

#### MARKETING

Curtailment of oil along the Atlantic seaboard introduced a new experience to people living in that area—the rationing of gasoline and fuel oil and the regulation of the use of automobiles for certain purposes. Although lack of fuel oil caused considerable inconvenience and some suffering, the rationing of gasoline probably necessitated more severe readjustments in living habits.

The responsibility of rationing was placed under control of the Office of Price Administration. Gasoline rationing was initiated in the 17 Atlantic Coast States and the District of Columbia on May 17. Rationing was extended to the rest of the country on December 1, but the purpose was to save tires rather than to conserve a deficient

supply of gasoline.

Heating-oil rationing was initiated in 30 Eastern and Midwestern States on October 1, after prohibition of sales during the summer. Rationing of heating oil was necessitated by an actual shortage in fuel oil as well as by difficulties in transportation. The problem of

A THE REST OF THE PARTY OF THE PARTY OF THE PARTY.

fuel oil, however, differed from that of gasoline in that abundant supplies of coal exist close to the centers of population, and fuel-oil users were urged to convert their facilities to coal-burning equipment wherever possible.

MOTOR FUEL

Domestic demand for motor fuel in 1942 was influenced by factors tending in opposite directions, but the elevating factors exerted less

influence than the depressing ones.

Accelerated military demand came to represent a material share of the consumption in 1942, and the increasing need for transportation of war workers took an additionally larger proportion of civilian con-

sumption as the year progressed.

The depressing factors were shortage of tires and rationing of gasoline. Realization of the limited future supply of tires was reflected in some curtailment of traffic early in 1942, although the momentum of the up-sweep of gasoline consumption largely concealed this retarding influence, and it was not until the second quarter that it began to be obvious.




FIGURE 8.—Trends of production, domestic demand, exports, imports, and stocks of motor fuel in the United States, 1918-42.

Transportation difficulties prompted the Office of Petroleum Coordinator to issue its Curtailment Order L-70, which limited deliveries of gasoline to the East Coast area and the Pacific Northwest, effective April 16, to two-thirds of normal. Considerable confusion resulted from the difficulty of service stations in accommodating customers, and limited sales and "No Gas" signs became common. This condition was improved only slightly when the Office of Price Administration, under authority from the War Production Board, instituted gasoline rationing on May 15 in the 17 East Coast States and the District of Columbia. Ration allowances for larger quantities than the retailers were permitted to obtain under Order L-70 complicated the retailers' difficulty in supplying the demand. Coupon rationing, instituted July 15, whereby the retailer exchanged

Comparative analyses of statistics for motor fuel in the United States in 1942, by months 1

[Thousands of barrels]

				1942			
	Jan.	Feb.	March	April	May	June	July
Production: Refinery gasoline:							
Cracked Straight-run	30, 324 22, 725	26, 006 19, 226	25, 629 20, 609	23, 504 18, 339	23, 130 19, 573	22, 423 17, 404	24, 08
Natural gasoline	7, 488	6,768	7,020	6, 257	6, 718	6, 558	18, 9
Natural gasoline Less L. P. G. sales Benzol	710 208	577 189	556 200	572	483	498	6, 80 55
Total production	60, 035	51, 612	52, 902	47, 528	48, 938	45, 887	49, 30
Daily average	1, 937	1, 843	1,707	1, 584	1, 579	1, 530	1, 59
Imports	14	85					1, 08
Exports	3, 131 101	2, 178 78	3, 053 98	2, 766 92	2, 567 83	3, 374 112	3, 42 11
Stocks, end of period:	00.40						
Finished gasoline	93, 489 4, 802	100, 186 5, 209	99, 184 5, 620	94, 127 6, 043	87, 461 6, 568	80, 080 6, 517	71, 65 6, 58
Total stocks	98, 291	105, 395	104, 804	100, 170	94, 029	86, 597	78, 24
Domestic demand	49, 223	42, 415	50, 440	49, 396	52, 512	49, 945	78, 24 54, 22
Daily average	1, 588	1, 515	1,627	1,647	1, 694	1, 665	
		J		1	1,051	1,000	1,74
	Allo	Sent	194	12			1,74 1941 (total)
	Aug.	Sept.		1	Dec.	Total	1941
Production: Refinery gasoline:		Sept.	194	12			1941
Refinery gasoline:	25, 387	23, 882	194 Oct.	Nov. 24, 433		Total	1941 (total)
Refinery gasoline: Cracked Straight-run	25, 387 19, 192	23, 882 19, 088	194 Oct.	Nov. 24, 433 19, 116	Dec.	Total 296, 928 233, 114	1941 (total)
Refinery gasoline: Cracked Straight-run Natural gasoline, etc Less L. P. G. sales	25, 387 19, 192 7, 028	23, 882 19, 088 6, 998	194 Oct. 24, 905 19, 997 7, 256	Nov. 24, 433 19, 116 7, 156	Dec. 23, 225 18, 891 7, 516	Total 296, 928 233, 114 83, 567	1941 (total) 344, 01: 279, 27: 80, 85
Refinery gasoline: Cracked Straight-run Natural gasoline, etc Less L. P. G. sales	25, 387 19, 192	23, 882 19, 088	194 Oct.	Nov. 24, 433 19, 116	Dec.	Total 296, 928 233, 114	1941 (total) 344, 01: 279, 273 80, 851 6, 281
Refinery gasoline: Cracked. Straight-run Natural gasoline, etc. Less L. P. G. sales Benzol. Total production	25, 387 19, 192 7, 028 502	23, 882 19, 088 6, 998 579	194 Oct. 24, 905 19, 997 7, 256 663	Nov. 24, 433 19, 116 7, 156 687	Dec. 23, 225 18, 891 7, 516 832	Total 296, 928 233, 114 83, 567 7, 195 597	1941 (total) 344, 01: 279, 27: 80, 85: 6, 28: 3, 43:
Refinery gasoline: Cracked. Straight-run Natural gasoline, etc Less L. P. G. sales Benzol  Total production Daily average Imports	25, 387 19, 192 7, 028 502	23, 882 19, 088 6, 998	194 Oct. 24, 905 19, 997 7, 256	Nov. 24, 433 19, 116 7, 156	Dec. 23, 225 18, 891 7, 516 832	Total  296, 928 233, 114 83, 567 7, 195 597 607, 011 1, 663	1941 (total) 344, 01: 279, 27: 80, 85! 6, 28: 3, 43: 701, 294
Refinery gasoline: Cracked Straight-run Natural gasoline, etc Less L. P. G. sales Benzol  Total production Daily average Exports Exports	25, 387 19, 192 7, 028 502 51, 105 1, 649 2, 936	23, 882 19, 088 6, 998 579 49, 389	194 Oct. 24, 905 19, 997 7, 256 663 51, 495 1, 661	24, 433 19, 116 7, 156 687 50, 018 1, 667	23, 225 18, 891 7, 516 832 48, 800 1, 574	296, 928 233, 114 83, 567 7, 195 597 607, 011 1, 663 99	1941 (total) 344, 013 279, 272 80, 855 6, 281 3, 435 701, 294 1, 921 333
Refinery gasoline: Cracked. Straight-run Natural gasoline, etc Less L., P. G. sales Benzol  Total production Daily average mports.	25, 387 19, 192 7, 028 502 51, 105 1, 649	23, 882 19, 088 6, 998 579 49, 389 1, 646	194 Oct. 24, 905 19, 997 7, 256 663 51, 495	24, 433 19, 116 7, 156 687 50, 018	Dec.  23, 225 18, 891 7, 516 832 48, 800	Total  296, 928 233, 114 83, 567 7, 195 597 607, 011 1, 663	1941 (total) 344, 01: 279, 27: 80, 85: 6, 28: 3, 43: 701, 294 1, 92: 27, 08: 27, 08:
Refinery gasoline: Cracked Straight-run Natural gasoline, etc. Less L., P. G. sales Benzol  Total production Daily average. mports Exports Daily average.  Daily average.	25, 387 19, 192 7, 028 502 51, 105 1, 649 2,936 95	23, 882 19, 088 6, 998 579 49, 389 1, 646 2, 020 67	194 Oct. 24, 905 19, 997 7, 256 663 51, 495 1, 661 3, 958	Nov. 24, 433 19, 116 7, 156 687 50, 018 1, 667 3, 478	Dec.  23, 225 18, 891 7, 516 832  48, 800 1, 574  3, 327	Total  296, 928 233, 114 83, 567 7, 195 607, 011 1, 663 99 36, 214	344, 01: 279, 27: 80, 85: 6, 28: 3, 43: 701, 294 1, 92: 27, 088; 74
Refinery gasoline: Cracked. Straight-run Natural gasoline, etc Less L. P. G. sales Benzol  Total production Daily average. mports. Exports. Daily average. Stocks, end of period: Finished gasoline.	25, 387 19, 192 7, 028 502 51, 105 1, 649 2, 936 95	23, 882 19, 088 6, 998 579 49, 389 1, 646 2, 020 67	194 Oct. 24, 905 19, 997 7, 256 663 51, 495 1, 661 3, 958	Nov. 24, 433 19, 116 7, 156 687 50, 018 1, 667 3, 478	Dec.  23, 225 18, 891 7, 516 832  48, 800 1, 574  3, 327	Total  296, 928 233, 114 83, 567 7, 195 607, 011 1, 663 99 36, 214	1941 (total) 344, 015 279, 279, 279, 280, 855 6, 281 3, 435 701, 294 1, 921 335 27, 083 27, 083
Refinery gasoline: Cracked Straight-run Natural gasoline, etc. Less L. P. G. sales Benzol  Total production Daily average.  Exports Daily average.  Stocks, end of period:	25, 387 19, 192 7, 028 502 51, 105 1, 649 2,936 95	23, 882 19, 088 6, 998 579 49, 389 1, 646 2, 020 67	194 Oct.  24, 905 19, 997 7, 256 663  51, 495 1, 661 3, 958 128	Nov.  24, 433 19, 116 7, 156 687  50, 018 1, 667 3, 478 116	Dec.  23, 225 18, 891 7, 516 832 48, 800 1, 574 3, 327 107	Total  296, 928 233, 114 83, 567 7, 195 607, 011 1, 663 99 36, 214 99	1941 (total) 344, 01: 279, 27: 80, 85: 6, 28: 3, 43: 701, 294 1, 92: 27, 083 27, 083
Refinery gasoline: Cracked Straight-run Natural gasoline, etc Less L. P. G. sales Benzol  Total production Daily average mports Daily average Stocks, end of period: Finished gasoline  Natural gasoline  Total stocks	25, 387 19, 192 7, 028 502 51, 105 1, 649 2, 936 95	23, 882 19, 088 6, 998 579 49, 389 1, 646 2, 020 67	194 Oct.  24, 905 19, 997 7, 256 663  51, 495 1, 661 3, 958 128  67, 669	Nov. 24, 433 19, 116 7, 156 687 50, 018 1, 667 3, 478 116 64, 224	Dec.  23, 225 18, 891 7, 516 832 48, 800 1, 674 3, 327 107 70, 772 4, 632	Total  296, 928 233, 114 83, 567 7, 195 607, 011 1, 663 99 36, 214 99  70, 772 4, 632	1941 (total) 344, 011 279, 27; 80, 85; 6, 28; 3, 43; 701, 294 1, 92; 27, 083 27, 083 27, 084 286, 159 4, 275 24, 437 90, 688
Refinery gasoline: Cracked. Straight-run Natural gasoline, etc. Less L. P. G. sales Benzol  Total production Daily average. mports. Exports. Daily average. Stocks, end of period: Finished gasoline.  Natural gasoline.	25, 387 19, 192 7, 028 502 51, 105 1, 649 2, 936 95 71, 403 6, 405	23, 882 19, 088 6, 998 579 49, 389 1, 646 2, 020 67 69, 293 6, 056	194 Oct.  24, 905 19, 997 7, 256 663 51, 495 1, 661 3, 958 128 67, 669 5, 424	Nov.  24, 433 19, 116 7, 156 687  50, 018 1, 667 3, 478 116  64, 224 4, 996	Dec.  23, 225 18, 891 7, 516 832  48, 800 1, 574  3, 327 107	Total  296, 928 233, 114 83, 567 7, 195 607, 011 1, 663 99 70, 772	1941 (total)  344, 01: 279, 27: 80, 85: 6, 28: 3, 43: 701, 294 1, 92: 27, 082 74  86, 413 2 86, 159 4 2, 275

the coupons he collected from the motorist for new supplies, largely eliminated the excessive demand, although there were frequent instances of dry tanks at service stations.

Nation-wide rationing of gasoline was instituted on December 1. Whereas rationing in the East Coast area resulted from insufficient supplies because of transportation difficulties, that consideration did not enter into the Nation-wide rationing, which was adopted to conserve tires.

Under the coupon system the basic ration was 4 gallons a week for each car, supplemental quantities being issued where it was necessary

Subject to revision.
 Preliminary figures for January 1, 1942

こうないというないというないとないというないとうないとうないというというないというないというないというないというないというないというないというないというないというないというないというないというないという

for a motorist to use his car to drive to war work or in performing war work, or where commercial users were assisting the production of war needs. During the winter coupon values were reduced to 3 gallons in the East Coast area, and early in 1943 pleasure driving was prohibited. When it was again permitted in March 1943, the basic ration was cut to 1½ gallons a week.

Domestic demand.—Domestic demand for motor fuel was 586,088,000 barrels, or 12 percent less than the 667,505,000 barrels in 1941. Automotive demand dropped, 18 percent—from 583,957,000

barrels in 1941 to 478,691,000 in 1942.

Distribution of domestic motor-fuel demand in the United States, 1938-42
[Thousands of barrels]

	1938	1939	1940	1941	1942 1
	-				
Passenger cars: Highway City	163, 092	171, 468	182, 816	204, 886	151, 170
	187, 923	198, 053	210, 199	238, 017	190, 414
Total passenger cars	351, 015	369, 521	393, 015	442, 903	341, 584
Frucks: Highway City	41,077	45, 478	47, 436	51, 604	54, 184
	61,616	67, 104	71, 220	75, 470	67, 923
Total trucksBusses	102, 693	112, 582	118, 656	127, 074	122, 107
	11, 765	12, 300	12, 975	13, 980	15, 000
Total automotive demandOther demand	465, 473	494, 403	524, 646	583, 957	478, 691
	57, 530	61, 106	64, 844	83, 548	107, 397
Grand total	523, 003	555, 509	589, 490	667, 505	586, 088

<sup>1</sup> Subject to revision.

Traffic statistics indicate that at many points truck traffic was greater on the highways in 1942 than in 1941 notwithstanding difficulty in obtaining tires and gasoline. This was particularly true in California, where there were large increases on some highways; there was even a gain in long-distance travel (indicated by trucks entering the State), which was 1 percent higher than in 1941, compared with a drop of 44 percent for passenger cars. The instances were rare where passenger-car traffic on the highways was greater than in 1941, some points in California being the principal exceptions.

Excepting California, city traffic was lower for both trucks and passenger cars, although traffic for the latter was affected considerably

more than the former.

Passenger cars in use July 1 declined from 27,635,000 in 1941 to 26,399,000 in 1942 and trucks from 4,817,200 to 4,677,000. Gasoline consumption per passenger car dropped from 16.03 barrels (673 gallons) in 1941 to 12.94 barrels (543 gallons) in 1942, and consumption per truck dropped from 26.38 barrels (1,108 gallons) to 26.11 barrels (1,097 gallons).

Exports.—Exports of motor fuel were 36,214,000 barrels in 1942

compared with 27,083,000 in 1941.

### Motor-fuel consumption per motor-vehicle unit in use on July 1, 1938-421

, 스타이 물에 발표하다. 1일 : 15 - 일하기를 하는		Passenger cars			Trucks	
Year	Consumption (thousands of barrels)	Number of vehicles	Consumption per unit (barrels)	Consumption (thousands of barrels)	Number of vehicles	Consumption per unit (barrels)
1938 1939 1940 <sup>2</sup> 1941 <sup>2</sup> 1942 <sup>2</sup>	351, 015 369, 521 393, 015 442, 903 341, 584	23, 875, 400 24, 342, 900 25, 385, 900 27, 635, 000 26, 399, 000	14. 70 15. 18 15. 48 16. 03 12. 94	102, 693 112, 582 118, 656 127, 074 122, 107	4, 258, 100 4, 340, 600 4, 531, 700 4, 817, 200 4, 677, 000	24. 12 25. 94 26. 18 26. 38 26. 11

<sup>&</sup>lt;sup>1</sup> Excludes gasoline consumed by busses and for nonautomotive uses.

<sup>2</sup> Subject to revision.

Production.—Motor-fuel output dropped 13 percent—from 701,294,000 barrels in 1941 to 607,011,000 in 1942. The production in 1942 comprised 233,114,000 barrels of straight-run gasoline, 296,928,000 barrels of cracked gasoline, 597,000 barrels of benzol, and 76,372,000 barrels of natural gasoline. Natural gasoline used in producing motor fuel consisted of 56,929,000 barrels blended at refineries, 19,248,000 barrels sold as such, and 195,000 barrels contributed to the increase in motor-fuel stocks.

### Production of gasoline in the United States in 1942, by methods of manufacture, districts, and months 1

			- 1 <u>- 1 - 1 - 1</u>	[Thous	ands of ba	rrels	<u> </u>					Т	<del></del>
Method and district	January	February	March	April	May	June	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total
Cracked: East Coast Appalachian. Indiana, Illinois, Kentucky, etc. Oklahoma, Kansas, and Missouri. Texas Inland Texas Gulf Coast. Louisiana Gulf Coast. Arkansas and Louisiana Inland. Rocky Mountain. California. Total straightrun	1,005 419 718 2,489	3, 731 1, 172 5, 558 2, 705 1, 262 7, 171 880 397 699 2, 438 26, 006	3, 138 1, 290 6, 393 2, 668 1, 356 5, 977 940 376 596 2, 895 25, 629 23, 2	2, 397 1, 094 5, 701 2, 698 1, 142 6, 008 910 477 495 2, 582 23, 504 22, 4	2, 335 1, 095 5, 783 2, 408 1, 209 5, 485 1, 023 350 699 2, 743 23, 130 21. 6	2, 774 1, 028 5, 841 2, 357 1, 134 5, 153 897 855 476 22, 428 21, 3	3, 044 1, 062 6, 057 2, 602 1, 109 6, 020 873 363 566 2, 384 24, 080 21, 5	3, 372 1, 043 5, 821 2, 640 1, 196 6, 478 909 381 621 2, 926 25, 387 22, 2	3, 257 1, 155 5, 804 2, 382 1, 133 5, 170 963 309 531 3, 178 23, 882 21, 1	3, 073 1, 107 5, 826 2, 522 1, 172 5, 992 1, 080 417 547 3, 169 24, 905 21, 4	3, 359 1, 169 5, 314 2, 471 1, 215 5, 796 947 423 699 3, 040 24, 433 21. 8	2, 882 999 5, 394 2, 309 1, 289 5, 353 1, 103 344 514 3, 038 23, 225 20. 5	38, 239 13, 483 69, 819 31, 054 14, 759 72, 989 11, 580 4, 611 7, 154 33, 290 296, 928 22, 2
Percent yield <sup>2</sup> Straight-run: East Coast. Appalachian Indiana, Illinois, Kentucky, etc. Oklahoma, Kansas, and Missouri. Texas Inland Texas Gulf Coast. Louisiana Gulf Coast. Arkansas and Louisiana Inland. Rocky Mountain. California	2, 792 901 5, 034 2, 462 1, 438 4, 908 917 586 807 2, 880	2, 136 815 4, 471 2, 230 1, 395 3, 487 685 566 609	2, 648 905 4, 615 2, 252 1, 369 3, 466 699 553 802 3, 300	1, 597 889 4, 479 2, 594 1, 368 2, 737 526 704 2, 797	1, 652 933 4, 577 2, 629 1, 456 3, 269 735 453 687 3, 182	1, 539 860 3, 739 2, 430 1, 664 2, 385 566 438 761 3, 022	1, 643 928 4, 435 2, 583 1, 725 2, 851 696 453 741 2, 899	-	1, 536 857 4, 563 2, 646 1, 685 2, 713 658 445 781 3, 204		1, 174 899 4, 731 2, 537 1, 553 2, 936 706 426 648 3, 506	1, 738 859 4, 128 2, 354 1, 475 3, 225 530 502 726 3, 354	22, 02: 10, 79: 53, 94: 29, 79: 18, 42: 37, 39: 8, 29: 5, 88: 8, 81: 37, 73:
Total cracked Percent yield 2	_ 22,725	19, 226 18. 2	20, 609 18. 6	18, 339 17. 5	19, 573 18. 3	17, 404 16. 5	18, 954 17. 1	16.8	19, 088 16. 8		19, 116 17. 0	18, 891 16. 7	233, 11 17.
Total production including natural gasoline:  East Coast	7, 847 2, 226 11, 936 6, 133 3, 67 15, 28 2, 119 1, 122 1, 619	2,029 10,560 5,307 1,963 11,963 1,770 1,038 1,374	2, 236 11, 540 5, 249 3, 236 10, 712 2, 020 994 1, 462	4, 060 2, 021 10, 659 5, 592 2, 898 10, 044 1, 848 1, 076 1, 241 6, 456	4, 014 2, 065 10, 911 5, 330 3, 137 10, 109 1, 996 1, 412 7, 100	4, 363 1, 926 10, 217 5, 088 3, 250 8, 929 1, 743 892 1, 268 6, 574	4, 755 2, 040 11, 158 5, 473 3, 327 10, 224 1, 836 974 1, 347 6, 477	2, 027 10, 962 5, 470 3, 355 10, 759 1, 933 7, 1, 391	5, 384 3, 339 9, 447 1, 875 915 1, 366	2, 155 11, 370 5, 466 3, 430 10, 315 2, 086 1, 064 1, 471 8, 048	2, 122 10, 707 5, 427 3, 311 10, 245 1, 973 967 1, 461 7, 739	5, 029 3, 193 10, 151 1, 983 965 1, 351 7, 661	61, 13, 24, 79; 131, 34' 64, 94; 39, 500 128, 18 23, 18 11, 87; 16, 76 85, 24
Total United States: 19421941	58, 40	0 49, 688 3 46, 841	50, 652 51, 950	45, 889 52, 009	46, 975 56, 188	44, 250 55, 136	47, 611 57, 714				48, 538 59, 480	47, 045 61, 640	586, 97 671, 11

<sup>1</sup> Subject to revision.

Based upon crude runs to stills.

The straight-run gasoline proportion of total motor fuel produced continued downward, declining from 39.8 percent in 1941 to 38.4 in The proportion of cracked gasoline also declined from 49.1 percent to 48.9, but natural gasoline increased from 10.6 percent to Blended natural gasoline, which increased from 6.8 percent to 9.4, accounted for the rise, as other natural gasoline declined from 3.8 percent to 3.2. Prohibition of the use of benzol in motor fuel is reflected in the decline from 3,435,000 barrels to 597,000. Statistics on disposition of the benzol manufactured have been restricted because of military secrecy. Some of it may have gone into the production of explosives and some into the production of styrene for polymerization with butadiene for the manufacture of synthetic rubber, but a considerable quantity, not included in the above figures, was being used in the production of cumene for aviation gasoline.

Yields.—Gasoline yields, subjected to conflicting forces during 1942, dropped to 39.7 percent from 44.2 percent in 1941. Primarily, the demand for motor fuel was lessened because of the rationing of tires throughout the year and the Nation-wide rationing of gasoline in Contrarily, the demand for heating oil and heavy oil fuel December. was considerably stronger, making it necessary for the usual balance of refinery operations to be modified to produce the minimum requirement of heavy oil without accumulating excessive stocks of gasoline. At the same time, the production of aviation gasoline was one of the most vital functions of the industry, and this kept the yield of gasoline

from dropping as low as it would have otherwise.
Yields of 22.2 percent for cracked and of 17.5 percent for straight-run gasoline were both lower than in 1941. The greater loss in cracked gasoline, however, reflected the diversion of cracking stock to fuel-oil uses, notwithstanding the heavy operations to supply base stock for aviation gasoline. The cracked-gasoline yield dropped from its peak of 25.8 percent in December 1941 to 21.3 percent in June 1942; it fluctuated about this point until the end of the year, when it dropped to 20.5 percent in December. The yield of straight-run gasoline dropped only about half as much-from 19.9 percent in December

1941 to 16.7 percent in December 1942,

The greatest drop in yield was in Texas; the Texas Gulf Coast district lost 7.7 percent—from 43.7 percent for 1941 to 36.0 for 1942 and Inland Texas lost 6.1 percent—from 54.6 percent to 48.5. yield in the Gulf Coast Louisiana district, where emphasis on aviation gasoline production caused the yield of cracked gasoline to rise during the year, experienced the smallest reduction of any district-from 37.7 percent to 37.3. Aviation gasoline production in the East Coast district also, notwithstanding the great need for fuel oil in this district, held the gasoline yield to a loss of only 1 percent-from 38.4 percent to 37.4.

Prices.—The average group 3 refinery price for gasoline in 1942 was 5.91 cents per gallon. Office of Price Administration Schedule 88, signed February 2, provided that prices in effect October 1, 1941, should be ceiling prices for petroleum and its products, except at service stations. As a consequence, the maximum price, which had been 6.375 cents during January and February, was fixed early in March at 6.00 cents—the lowest price prevailing on October 1, 1941. Fluctuations during the balance of the year represent averages between this ceiling price and lower prices for which gasoline sold.

Average monthly prices of gasoline in the United States, 1941-42, in cents per gallon

	Jan.	Fe	b.	Mar		Apr.	м	ау	June	July	,	Aug.	Sept.	Oct.	Nov.	Dec.	Aver- age for year
		70		• • •	7		Г	_			1			A			9561
1941					1			-	- (	100	1		2.1	100			
Monthly average at refiner-					1						1	111	+14,54	2.5	100		- 141
ies in Oklahoma, 72-74					-				1.1.		1			- 6 40		امد ما	- 0
octane 1	4, 72	4.	69	4.7	1	5.09	5.	47	5. 99	6.1	8	6. 19	6. 19	6. 18	6. 19	0. 18	5. 6
A verage of 50 cities on 1st of	٠.	1 1	-				1	1.		. 2	1			100			
month: 2 Dealer's net	8. 54	Q.	54	8 6	2	8 78	9	40	9 85	9. 9	4	10.04	10.02	10.04	10.02	10.04	9.4
Service station (include			1		- 1		1								1	-	
ing State tax)	16. 57	16.	58	16. 6	57	16. 82	17.	53	18. 14	18. 2	6	18. 32	18.39	18. 49	18. 49	18. 52	17. 7
		_	=		= :		-	=	—	-	= :			_	-		777
1942	***						١.										
Monthly average at refiner-			1		1		1				-						
ies in Oklahoma, 72-74			. 1	100					6.00	12						100	
octane 1	6. 19	6.	16	5. 7	77	5. 72	5.	76	5.81	5.8	7	5.92	5.94	5.94	5.94	5.94	5.9
A verage of 50 cities on 1st of	100		- 1											1			100
month: 2				10.		10.0	-		10 20	1		11 00	10. 33	10 2	10 27	10 37	10.4
Dealer's net	9.98	10.	10	10.	ιυ	10. 2	10.	40	10. 99	11. 0	'-	11. 20	10. 00	10. 0	10.00	10.01	-0
Service station (includ- ing State tax)	10.41	10	50	10	54	10 7	112	27	18 87	10 8	اء	10 70	18.86	18.8	18.87	18, 91	18.9

The 50-city service-station average price, which gained 1.84 cents during 1941, was permitted by the Office of Price Administration (see Maximum Price Order 137) to rise another 1.45 cents from January to July 1942, only to be reduced almost 1 cent in August. The year ended with a net gain of .52 cent. Most of the gain represented compensation to the dealers along the East coast for the increased cost of transporting gasoline by tank car instead of by boat, as is normal in peacetimes. The Defense Supplies Corporation assumed 2.5 cents per gallon of this cost in August—the same amount prices had been raised in the East coast area in June—and retail prices were reduced a corresponding sum. General price changes in the East coast area were as follows:

January 23, plus 0.3 cent. March 27, plus 0.5 cent. April 30, plus 0.4 cent. June 29, plus 2.5 cents. August 5, minus 2.5 cents.

The net change for the East coast cities in general was an increase

of 1.2 cents.

Although there were a number of changes during the year in some cities in the Central States, there was little difference in the price at the end of the year from that at the beginning, except for Des Moines, Iowa, and Little Rock, Ark., where prices increased 3 cents. These two increases and a rise of 1.4 cents in St. Louis were responsible principally for an increase of .39 cent in the average price for the cities in the Central States. Even with this rise, these cities had the lowest average price-13.31 cents, ex-tax-of any section of the country.

Decreases in the Rocky Mountain cities brought the average price of 15.15 cents below that of the unchanged Pacific coast area and only slightly above that of the East Coast cities-15.11 cents. Changes were most violent in Salt Lake City, Utah, where cuts reduced the price 4.5 cents in February. One cent of the cut was restored in

<sup>&</sup>lt;sup>1</sup> National Petroleum News. <sup>2</sup> American Petroleum Institute; compiled by The Texas Co.

March, another cent in October, and 1.5 cents more in November making the year-end price only 1 cent less than that at the beginning of the year. One cent of a drop of 3.6 cents in Denver in July was restored in August, leaving the price at the end of the year 2.6 cents less than at the beginning. A loss of 2.0 cents in the price at Butte, Mont., was the only other change in the Rocky Mountain cities in-

cluded in the 50-city price average.

Twin Falls, Idaho, still had the most costly gasoline for the motorist; the service-station price in that city was 25.6 cents, including 6.6 cents tax, and Boise, Idaho, followed with a price of 24.1 cents. Birmingham, Ala., with a price of 23.5 cents (including 8.5 cents city, State, and Federal taxes) and Charleston, S. C. (with a price of 23.2 cents, including 7.5 cents taxes), were next. The price in Kansas City, Mo., of 15.6 cents was lowest, with the 15.9-cent price in Wichita, Kans., next, followed by St. Louis, Mo. (16.3 cents); all three prices included 4.5 cents taxes.

There were no changes in either State or Federal motor-fuel tax rates during 1942, but the revenue from State gasoline taxes dropped from \$950,956,410 in 1941 to \$839,457,000 in 1942, and that from

Federal gasoline taxes from \$371,135,781 to \$336,684,645.

Aviation gasoline.—The program for the production of aviation gasoline launched in 1941 was well under way by the end of 1942, when approximately 16 times as much 100-octane gasoline was being produced as at the beginning of 1941. With the largest part of the proposed plants yet unfinished, however, that production was still

considerably short of the goal of 250,000 barrels a day.

The change from production of motor fuel to production of highoctane gasoline sufficient to fly the planes of the United States and its
allies can be appreciated better when it is realized that iso-octane was
merely a laboratory curiosity until a few years ago; that the first
output of 100-octane gasoline in commercial quantities was to fill a
War Department order in 1934 for 1,000 gallons; that the first commercial catalytic polymerization plant was put in operation in 1937
and the first alkylation plant in 1938—in fact, it was only recently
that the chemical world learned that olefins could be combined with
parafins, from which discovery the alkylation process developed.

Stocks.—Stocks of finished and unfinished gasoline mounted to a record peak of 108,297,000 barrels on February 28, 1942, then plunged to 73,216,000 barrels on November 30—the lowest point since 1939. They totaled 80,126,000 barrels at the end of the year, compared with 93,844,000 at the end of 1941, although the smaller amount on hand at the end of 1942 represented 63.3 days' supply compared with

55.6 days' supply on hand at the end of 1941.

The Gulf Coast Texas and Louisiana, California, and Inland Louisiana-Arkansas districts had larger stocks at the end of 1942 than at the end of 1941; in fact, stocks in the last district more than doubled during the year. In the East Coast district the stocks dropped 47 percent. Such a severe cut was made possible in this district by pooling stocks and eliminating brand identities, by stopping cross-hauls, and by pooling facilities.

Figure 9 shows the monthly quantities of finished gasoline stocks, in millions of barrels, from January 1, 1940, to December 31, 1942. The figures for days' supply on the chart represent the quantity of

The state of the s

finished gasoline on hand at the end of the month, divided by the total

demand for the succeeding month.

Figure 9 also shows the stocks of distillate fuel oil for the same years, to stress the contrast in seasonal variations in stocks of the two products. It also shows how distillate fuel-oil stocks, although not declining as greatly as gasoline stocks, were on a considerably lower level throughout most of 1942 than in 1941 despite a demand in 1942 9 percent higher than that in 1941.




FIGURE 9.—Stocks of finished gasoline in the United States, 1940-42, by months, with figures representing days' supply at certain periods; also stocks of distillate fuel oil, 1940-42, by months.

Days' supply 1 of motor fuel on hand in the United States at end of month, 1940-42

		1940			1941			1942 3	
Month	Fin- ished gasoline	Nat- tural gasoline	Total motor fuel	Fin- ished gasoline	Nat- ural gasoline	Total motor fuel	Fin- ished gasoline	Nat- ural gasoline	Total motor fuel
January February March April May June July August September October November December	62. 3 61. 3 58. 2 54. 5 48. 3 48. 1 44. 2 42. 7 42. 0 42. 9 47. 0 51. 0	32243991298977 33333344333333	65. 6 64. 5 61. 4 57. 9 51. 0 48. 3 46. 9 45. 9 46. 7 50. 9	53. 0 53. 5 47. 5 44. 4 42. 5 39. 0 36. 2 36. 4 38. 8 42. 6 }	3.5 3.28 2.88 2.9 3.0 3.0 3.7 2.5 2.4	56. 5 56. 7 50. 6 47. 2 45. 0 39. 2 38. 2 39. 1 41. 3 45. 0 53. 6	58. 7 58. 1 57. 1 53. 0 49. 2 43. 1 43. 1 41. 3 40. 0 37. 7 46. 7 55. 9	3.0 3.2 3.4 3.7 3.5 4.0 3.5 3.6 3.6	61. 7 61. 1 60. 3 56. 4 52. 9 46. 6 47. 1 45. 0 43. 5 40. 7 50. 3

<sup>1</sup> Stocks divided by the daily average total demand (domestic demand plus exports) for succeeding month.

2 Subject to revision.

3 For comparison with 1941.

3 Subject to revision.

## Stocks of gasoline in the United States in 1942, by districts and months <sup>1</sup> [Thousands of barrels]

District	January 31	Febru- ary 28	March 31	April 30	May 31	June 30	July 31	August 31	Septem- ber 30	October 31	Novem- ber 30	Decem- ber 31
Finished gasoline: 2												
East Coast	19,011	18, 378	16, 139	14, 625	12, 209	13, 703	11, 982	12, 723	12, 054	11, 221	10, 150	9, 926
Appalachian	3, 667 20, 380	3, 709 22, 111	3, 793 22, 568	3, 713 20, 977	3, 043 18, 453	2, 271 15, 977	2, 170 14, 497	2, 360 13, 985	2,406	2, 245	2, 034	2, 356
Indiana, Illinois, Kentucky, etc Oklahoma, Kansas, and Missouri	9, 381	10, 293	9, 921	9, 439	8, 428	7. 326	6. 404	5, 886	13, 330 5, 668	12,858 5,627	11, 614 5, 118	14, 369 5, 984
Texas Inland	3, 126	3, 429	3, 527	3, 356	2 868	2, 421	1, 833	1, 795	1, 752	1, 709	1, 490	2, 023
Texas Gulf Coast	15 923	19, 136	19, 861	18, 979	19, 916	17, 555	15, 694	15, 740	14, 827	14, 962	14, 407	14, 322
Louisiana Gulf Coast	3, 780	4, 031	4,000	3, 899	3, 640	3, 142	3, 390	3, 533	3, 689	3, 368	3, 407	3, 600
Arkansas and Louisiana Inland	1.158	1, 339	1, 360	1, 270	1, 206	1, 223	1, 130	931	1. 171	1, 287	1, 165	1, 709
Rocky Mountain California	2, 209	2, 660	2,817	2, 576	2,488	2, 189	1, 907	1. 546	1, 202	1, 110	1,076	1, 347
California	14, 854	15, 100	15, 198	15, 293	15, 210	14, 273	12,650	12, 904	13, 194	13, 282	13, 763	15, 136
Total finished gasoline	93, 489	100, 186	99, 184	94, 127	87, 461	80, 080	71, 657	71, 403	69, 293	67, 669	64, 224	70, 772
Unfinished gasoline:												
East Coast	931	913	769	897	827	733	994	1, 188	1, 245	1,052	1.111	1,010
Appalachian	357	370	403	389	410	405	423	417	409	372	321	306
Indiana, Illinois, Kentucky, etc	650	709	643	611	543	538	523	653	732	763	762	995
Oklahoma, Kansas, and Missouri Texas Inland	412	415	496	487	383	396	353	276	273	254	280	289
Texas Inland	490	484	205	362	346	249	162	195	172	182	179	221
Texas Gulf Coast	2, 129	2, 493	2, 515	2, 451	2, 303	2, 302	2, 280	2, 164	2, 596	2, 902	2, 951	2,871
Louisiana Gulf Coast Arkansas and Louisiana Inland Rocky Mountain	406	413	357	338	289	304	395	278	402	347	326	376
Arkansas and Louisiana Inland	10 93	8	8	7	8	6	4	5	5	3	5	- 3
California.	2, 246	103 2, 203	109	91 2, 062	98	105	106	103	100	98	93	88
			2, 044		2, 013	2, 399	2, 549	2,844	2, 919	2, 980	2, 964	3, 195
Total unfinished gasoline	7, 724	8, 111	7, 549	7, 695	7, 220	7, 437	7, 789	8, 123	8,853	8, 953	8, 992	9, 354
Total finished and unfinished:										28 (1)		
East Coast	19, 942	19, 291	16,908	15, 522	13, 036	14, 436	12, 976	13, 911	13, 299	12, 273	11, 261	10, 936
Appalachian	4, 024	4, 079	4, 196	4, 102	3, 453	2, 676	2, 593	2, 777	2,815	2, 617	2, 355	2, 662
Indiana, Illinois, Kentucky, etc Oklahoma, Kansas, and Missouri Texas Inland	21,030	22, 820	23, 211	21, 588	18, 996	16, 515	15, 020	14, 638	14, 062	13, 621	12, 376	15, 364
Okianoma, Kansas, and Missouri	9, 793	10, 708	10, 417	9, 926	8, 811	7, 722	6, 757	6, 162	5, 941	5, 881	5, 398	6, 273
Texas Gulf Coast	3, 616	3, 913	3, 732	3, 718	3, 214	2,670	1, 995	1,990	1,924	1,891	1,669	2, 244
Louisiana Gulf Coast	18, 052 4, 186	21, 629 4, 444	22, 376 4, 357	21, 430 4, 237	22, 219	19, 857	17, 974	17, 904	17, 423	17,864	17, 358	17, 193
Arkansas and Louisiana Inland	1, 168	1, 347	1, 368	1, 277	3, 929 1, 214	3, 446 1, 229	3, 785 1, 134	3, 811 936	4, 091 1, 176	3, 715 1, 290	3, 733 1, 170	3, 976 1, 712
Arkansas and Louisiana Inland Rocky Mountain	2, 302	2, 763	2, 926	2, 667	2, 586	2, 294	2, 013	1, 649	1, 176	1, 290	1, 170	1, 712
California	17, 100	17, 303	17, 242	17, 355	17, 223	16, 672	15, 199	15, 748	16, 113	16, 262	16, 727	18, 331
Total United States: 1942		108, 297	106, 733	101, 822	94, 681	87, 517	79, 446	79, 526	78, 146	76, 622	73, 216	80, 126
			1 1		,,				1		1.0	94, 098
1941	90, 366	95, 558	98, 706	95, 769	92, 831	89, 758	84, 701	80, 377	79, 963	82, 303	87, 278	3 93, 844

<sup>1</sup> Subject to revision.

<sup>&</sup>lt;sup>2</sup> Includes stocks of finished gasoline at refineries, bulk terminals, and in pipe lines.

<sup>&</sup>lt;sup>3</sup> For comparison with 1942.

Production and consumption by States.—Although the relative proportion of gasoline produced by Texas dropped from 32 percent in 1941 to 29 in 1942, its output was almost twice the 15 percent of California, next in importance. Percentages for other important States were: Illinois, 8; Pennsylvania and Indiana, 7 each.

Military requirements caused gasoline consumption in California and Texas to increase in 1942, but tire and rationing restrictions brought material declines for New York, Pennsylvania, and other States. As a result, the States did not follow their usual order of importance. The percentage consumption of the principal States was as follows: California, 9.5; Texas, 7.4; New York, 6.7; Ohio, 6.2; Illinois, 6.0; Pennsylvania, 5.9; Michigan, 5.1.




FIGURE 10.—Consumption of gasoline in the United States, 1941-42, by States.

Production and consumption of gasoline in the United States, 1940-42, by States

	19	40	19	41	194	12 1
State	Produc- tion	Consump- tion <sup>2</sup>	Produc- tion	Consump- tion 2	Produc- tion	Consump- tion 2
Alabama	(3)	6, 307	(3)	7, 819	(3)	7, 376
Arizona		2,637		3,051		3,029
Arkansas	3,702	4,546	4,044	5, 340	4,033	4, 92
California	4 76, 885	45,904	4 85, 734	51, 251	4 85, 248	53, 220
ColoradoConnecticut	2,020	5,976	2, 334	6,358	2,312	5, 832
Connecticut		9,068		10,035		8, 03
Delaware		1,495		1,622		1,300
District of Columbia		4,027		4, 561		3, 568
Florida		9, 713		11, 326		10, 503
Georgia	5 4, 329	9,346	5 4, 983	10,713	5 3, 104	9,096
[daho	(6)	2, 547	(6)	2,786	(6)	2, 526
Illinois	7 41, 386	35, 944	7 49, 377	38, 987	7 46, 825	33, 707
ndiana	43, 180	17, 175	43, 704	19, 564	39, 017	17,658
owa		13, 637		14, 578		12, 95
Kansas	8 33, 208	11,943	8 37, 434	12,872	8 33, 878	11,600
Kentucky	97.049	6,954	9 8, 523	7, 939	9 7, 949	6, 698
Louisiana	3 23, 673	6,627	3 30, 300	8, 179	3 31, 024	7, 18
Maine		3,747		4, 138		3, 188
Maryland	(5)	7, 491	(5)	8, 703	(5)	7, 46
Massachusetts	10 6, 554	17, 791	10 5, 791	19, 155	10 5, 023	14, 454
Michigan	10, 216	29, 979	11, 180	33, 149	11,073	28, 613
Minnesota	(7)	13, 861	(7)	14, 481	(7) (8)	13, 030
Mississippi	(3)	5, 219	(3)	6, 163	(3)	6, 079
Missouri	(8)	16, 623	(8)	18, 472	(8)	15, 336
Montana	3, 836	3, 276	4, 293	3, 533	4, 245	3, 02
Nebraska	(8)	5, 629	(8)	5, 989	(8)	5, 59
Nevada		1,043		1,102		1,160
New Hampshire		2, 282		2, 582		1,84
New Jersey	25, 451	22,023	28, 312	23, 838	19,677	19, 24
New Mexico	1, 121	2,630	1, 193	2,909	1,473	2, 349
New York	7,826	46, 918	9,044	48, 797	8, 220	37, 740
North Carolina		10, 938		12, 923		10, 13
North Dakota		3, 638		3, 947		3, 92
Ohio	31, 603	35, 022	34, 804	39, 031	34, 706	35, 06
Oklahoma	32, 603	10, 584	34, 190	11,368	31,071	10,06
Oregon		6, 250		7, 230		6,66
Pennsylvania	46, 550	37, 666	51, 431	40, 594	39, 149	33, 07
Rhode Island	(10)	3, 190	(10)	3, 507	(10)	2,83
South Carolina	(5) (8)	5, 577	(5)	6, 555	(5)	5, 18
South Dakota		3,422	(8)	3, 634	(8)	3, 419
Tennessee	(9)	7,785		9,186	(9)	8, 59
Texas	184, 885	33,806	212, 347	39, 839	167, 681	41, 45
Utah	(6)	2, 552	(0)	2,783	(0)	2, 69
Vermont		1,686		1,790		1, 28
Virginia		9, 943		11,842		9, 59
Washington	(4)	9,024	(4)	10, 536	(4) 0 500	10, 56
West Virginia	2,017	5, 262	2, 317	5,719	2, 529	4,66
Wisconsin	6 9, 185	14,049 1,668	(7) 6 9, 775	15, 148 1, 882	<sup>(7)</sup> 68,734	13, 60 1, 47
Wyoming	9, 185	1,008	· 8, 115	1,082	* 0, 104	1, 47

Subject to revision.
 American Petroleum Institute.
 Alabama and Mississippi included with Louisi-

<sup>4</sup> Washington included with California.

<sup>5</sup> Maryland and South Carolina included with Georgia.

 Idaho and Utah included with Wyoming.
 Minnesota and Wisconsin included with Illinois.
 Missouri, Nebraska and South Dakota included with Kansas.

9 Tennessee included with Kentucky.
10 Rhode Island included with Massachusetts.

Distribution.—The methods of moving petroleum products were greatly altered by the war, as much of the burden was shifted from marine to rail transportation. Gasoline shipments by barge and tanker from the Gulf Coast to the East Coast district amounted to only 32,289,000 barrels in 1942 compared with 130,534,000 in 1941. Movement by barge from Texas and Louisiana to points on the Mississippi River, however, increased from 13,736,000 barrels in 1941 to 15,960,000 in 1942.

Pipe-line shipments of motor fuel increased from 111,077,000 barrels in 1941 to 125,341,000 in 1942. Details of pipe-line construction and other developments in transportation appear in the section on

Transportation.

# Shipments of motor fuel by pipe lines in the United States in 1942, by months [Thousands of barrels]

5625							1942							
	January	Febru- ary	March	April	Мау	June	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total	1941 total
Motor fuel turned into lines. Motorfuel delivered from lines. Shortage. Stocks in lines and working.	10, 122 9, 151 35	8, 478 7, 937	9,846 9,855 10	9, 895 10, 338 139	10, 453 11, 112 6	9, 694 9, 953 4	10, 242 10, 412 138	10, 615 10, 912 45	10, 538 10, 004 144	12, 255 12, 260 45	11, 664 12, 144 22	12, 430 11, 263 90	126, 232 125, 341 677	112, 976 111, 077 615
tanks, end of month	7, 294	7, 836	7, 817	7, 235	6, 570	6, 307	5, 999	5, 657	6, 047	5, 997	5, 495	6, 572	6, 572	6, 358

<sup>&</sup>lt;sup>1</sup> Overage.

### KEROSINE AND RANGE OIL

An expected increase in domestic demand for kerosine in 1942 did not materialize, owing to transportation difficulties and rationing of deliveries in some areas; consequently, the 1942 total was practically the same as 1941 requirements. Exports of kerosine declined in 1942; while imports, though of relatively unimportant volume, more than doubled the 1941 total. Lower crude runs to stills and a smaller percentage yield resulted in less kerosine production in 1942 than in A. deficiency in kerosine supply in 1942 due to a lower output resulted in a heavy draft on stocks.

Petroleum refiners produced 7 percent less kerosine in 1942 than in 1941, the output declining from 72,586,000 barrels in 1941 to 67,474,000 in 1942. The yield dropped slightly from 5.2 percent in 1941 to 5.1 percent in 1942; however, lower runs of crude petroleum to stills in 1942 (5 percent under the 1941 volume), tanker transportation difficulties, and the effort of refiners to produce much-needed fuel oils were the principal reasons for the smaller production of kerosine.

Comparative analyses of statistics for kerosine in the United States, 1941-42, by months and districts

Month and district	(thous	luction sands of rrels)	Yield (	percent)	mand	stic de- (thou- f barrels)	Stocks (thousand of barrels)		
	1941	1942 1	1941	1942 1	1941	1942 1	1941	1942 1	
By months: January February March April May June July August September October November December  Total United States	5, 888 6, 033 6, 068 6, 033 5, 218 5, 406 5, 850 5, 949 6, 355 6, 443 6, 682	6, 634 6, 133 6, 035 5, 529 5, 302 4, 929 5, 134 5, 340 5, 421 5, 907 5, 759 5, 351	6.9 5.4 5.5 5.5 4.5 4.5 4.9 5.3 5.3	5.6 5.8 5.5 5.3 4.9 4.6 4.7 4.8 5.1 4.7	7, 769 6, 484 6, 821 5, 549 4, 504 3, 918 4, 270 5, 621 5, 519 7, 080 7, 404	9, 750 7, 690 7, 230 5, 516 4, 580 3, 653 3, 266 4, 039 5, 012 5, 367 5, 684 7, 827	8, 312 7, 634 6, 724 7, 063 8, 421 9, 609 10, 635 11, 636 11, 662 11, 670 10, 843 9, 599 { 9, 599 2 14, 515	11, 007 9, 324 7, 900 7, 806 8, 433 9, 497 10, 933 12, 176 12, 363 12, 645 12, 630 10, 064	
By districts: East Coast Appalachian Indiana, Illinois, Kentucky, ete. Oklahoma, Kansas, and Missouri Texas Inland Texas Gulf Coast Louisiana Gulf Coast Arkansas and Louisiana Inland. Rocky Mountain California.	9, 169 3, 166 11, 864 7, 505 2, 987 24, 448 7, 304 3, 080 906 2, 157	7, 929 3, 640 15, 802 8, 984 3, 015 17, 364 5, 219 2, 460 698 2, 363	4. 2 5. 9 4. 7 5. 9 4. 5 6. 7 13. 5 10. 5 2. 7 1. 0	4. 9 6. 3 6. 0 6. 9 4. 4 5. 7 9. 8 8. 6 2. 0 1. 0	(3)	(3)	6, 561 366 1, 660 678 282 3, 036 630 246 129 927	2, 853 337 1, 554 576 178 2, 456 1, 290 214 81 525	
Total United States	72, 586	67, 474	5. 2	5. 1	69, 469	69, 614	<sup>2</sup> 14, 515	10,064	

East Coast, Texas Gulf Coast, Louisiana Gulf Coast, and Arkansas and Louisiana Inland, important districts for the production of

Subject to revision.
 New basis to compare with 1942. Monthly figures for 1941 do not include bulk terminal stocks which tere not available until December 31, 1941.

kerosine, all showed sharp declines in production in 1942 compared with 1941. An exception to this general trend was the Indiana-Illinois refinery district, an area second in national importance as a source of kerosine, where production increased by a third in 1942 over 1941. Gains in kerosine output were also realized in the Appalachian, Oklahoma-Kansas, Texas Inland, and California districts. It should be noted that the Gulf refinery districts, which depend on tankers to transport kerosine to East coast and export markets, showed declines in production, whereas inland districts, which could make rail shipments advantageously to important consuming centers, reported gains in output. In other words, transportation, or the lack of it, largely determined kerosine production in most districts during 1942.

The indicated domestic demand for kerosine in 1942—69,614,000 barrels, calculated from production, change in stocks, exports, and imports—varied little from the 1941 total—69,469,000 barrels. It is believed that the 1942 quantity would have increased at least 5 percent had normal conditions prevailed. The potential market demand was not fully supplied, especially in the North Atlantic Coast area,

because of the tanker shortage.

The shrinkage in kerosine exports during present war years continued into 1942, when shipments abroad totaled 2,729,000 barrels compared with 3,221,000 in 1941. Available information for 1941 shows that most of the kerosine shipped abroad went to the United Kingdom (1,941,000 barrels) and to Brazil (223,000 barrels), while in 1942 the United Kingdom and its Dependencies received the larger share—United Kingdom 1,671,000 barrels, Canada 236,000, and Australia 179,000.

Imports of kerosine, though relatively unimportant in volume,

increased from 191,000 barrels in 1941 to 418,000 in 1942.

Year-end kerosine stocks for 1941 were revised to include quantities held at bulk terminals. Kerosine in storage at the close of 1942 was 31 percent below the comparative total for 1941—a draft made necessary in order to supplement a curtailed supply resulting from lower refinery production. Kerosine stocks of 10,064,000 barrels in 1942 represented a 40-day supply at the prevailing rate of demand compared with 14,515,000 barrels or a 61-day supply at the close of 1941.

Kerosine inventories on December 31, 1942, were lower in all refinery districts than at the end of 1941 except for the Louisiana Gulf Coast where a gain was indicated. The stock increase in the Louisiana Gulf district (1,290,000 barrels in 1942 compared with 630,000 in 1941) represents a "back-up" of kerosine intended for East coast and other markets due to the shortage of tankers. The pronounced drop in kerosine stocks in the East coast from 6,561,000 barrels at the end of 1941 to 2,853,000 for 1942 was outstanding. Oil companies operating on the Atlantic coast could not obtain their usual supplies of kerosine from the Gult area because of the tanker situation, so a drastic draft of local stocks was necessary. The extent of the shrinkage in the kerosine inventory on the East coast in 1942 is better illustrated when it is noted that such supplies represented 45 percent of total national stocks in 1941 and only 28 percent in 1942. Higher kerosine production in the Indiana-Illinois district in 1942 and the difficulty of moving the surplus freely to other markets kept

up stocks there almost to the 1941 level. Kerosine held in the Texas Gulf coast declined from 3,036,000 barrels in 1941 to 2,456,000 in 1942 as supplies were taken from storage to supplement a declining production. Increased kerosine output in California was not adequate to meet the demand in 1942 so an added quantity was taken from stocks.

Sales of kerosine in the United States, 1940-41, by regions, States, and uses 1
[Thousands of barrels]

Region and State	Sold a	as range oil	Trac	tor fuel	All ot	her uses	T	otal
	1940	1941	1940	1941	1940	1941	1940	1941
Pacific Coast:								
California	91	98	13	19	985	1 100	1 000	
Oregon	11	10	6	10	53	1, 188 116	1,089	1, 305
Washington	5	14		10	130	157	70 135	136
Oregon Washington Arizona	5	1 12	2	5	90	133	97	171
Nevada				"	. 11	26	11	150 26
Rocky Mountain: Idaho		100				20		20
Idaho	1	2	9	11	9	19	19	32
Montana	34	39	97	45	50	69	181	153
Wyoming	4	8	29	15	17	18	50	41
Utah	9	5	14	4	14	16	37	25
Colorado	20	28	69	54	46	37	135	119
New Mexico	18	15	41	53	61	95	120	163
North Central:		-				1		100
North Dakota	54	65	168	129	66	56	288	250
South Dakota	102	84	143	115	59	63	304	262
Minnesota	278	307	262	193	457	516	997	1,016
Nebraska	130	158	180	186	144	160	454	504
Iowa	191	217	282	194	659	645	1, 132	1,056
Wisconsin	188	221	208	149	516	508	912	878
Illinois	1, 114	1, 216	340	258	1, 615	1, 551	3,069	3, 025
Indiana	179	200	168	197	1, 211	1, 183	1, 558	1, 580
Michigan	334	282	136	95	756	801	1, 226	1, 178
Ohio	322	312	212	237	791	741	1,325	1, 290
Kentucky	60	79	60	59	510	533	630	671
Tennessee South Central:	116	102	68	78	460	483	644	663
Missouri	000	100		1				
Kansas	380	423	157	166	653	610	1, 190	1, 199
Texas	178 306	163	191	158	209	226	578	547
Oklahoma	148	411	509	516	1,611	1,740	2, 426	2, 667
Arkansas	148	146	212	268	550	524	910	938
Louisiana	140	136	150	190	420	460	710	786
Mississippi	36	108	101	162	714	730	957	1,000
Alabama	61	52 66	144	130	376	346	556	528
New England:	01	00	18	44	377	405	456	515
Maine	1, 562	1, 697			مد ا			
New Hampshire	894	906		4 2	42	36	1,604	1, 737
Vermont.	560	638		1	39	34	933	942
Massachusetts	13, 029	12, 931		1	73	88	633	727
Rhode Island	2, 547	2 /3/			460	453	13, 489	13, 384
Connecticut	3, 793	2, 434 3, 852	2		80	93	2,627	2, 527
Middle Atlantic:	0, 100	0,002			140	126	3, 935	3, 978
New York	7, 110	7, 261	148	117	1, 352	1 407	ا میما	
New Jersey Pennsylvania	3, 316	3, 437	28	22	1, 295	1, 427	8, 610	8, 805
Pennsylvania	830	919	124	162	1, 412	1, 170	4, 639	4, 629
Delaware	118	95	4	3	63	1, 450	2, 366	2, 531
Maryland	529	490	28	9		68	185	166
District of Columbia	78	85	5	9	685 92	624	1, 242	1, 123
South Atlantic:	••	00	١	9	92	82	175	176
Virginia	198	173	19	11	658	687	875	071
West Virginia	29	53	10	13	191	168		871
North Carolina	573	665	80	76	678	710	230	234
South Carolina	171	170	32	31	425	429	1, 331	1, 451
Georgia	214	277	76	105	425		628	630
Florida	507	599	138	162	460	549 519	789 1, 105	931 1, 280
·				102	400	919	1, 100	1, 280
Total United States	40, 715	41,661	4,683	4, 467				

<sup>&</sup>lt;sup>1</sup> Figures for 1942 by States not yet available.

The Bureau's annual survey of kerosine sales shows deliveries of 68,996,000 barrels in 1941 compared with 67,662,000 in 1940, a gain of 2 percent. The above quantities were divided as follows: Range oil, 41,661,000 barrels in 1941 and 40,715,000 in 1940; tractor fuel, 4,467,000 barrels in 1941 and 4,683,000 in 1940; all other uses, 22,868,000 barrels in 1941 and 22,264,000 in 1940. The range oil market absorbed about 60 percent of total kerosine deliveries for both 1940 and 1941.

Some No. 1 fuel oil, which varies only slightly from kerosine, is also sold for range fuel. This light fuel oil, (4,449,000 barrels in 1941 and 3,977,000 in 1940) must be added to the kerosine reported as range fuel to determine total requirements for range oil. Making this adjustment, total sales of range oil were 46,110,000 barrels in 1941

compared with 44,692,000 in 1940, a gain of 3 percent.

Representative kerosine prices in 1942 changed very little from those prevailing during the last 6 months of 1941. An average monthly price of 4.56 cents a gallon for 41°-43° gravity water-white kerosine at refineries in Oklahoma, starting in June 1941, was maintained until March 4, 1942, when it dropped to an average of 4.44 cents a gallon, a quotation that ruled until the end of the year. The tank-wagon price of kerosine at Chicago (10.3 cents a gallon dating from June 1941) remained unchanged until December 31, 1942, when it increased to 10.6 cents a gallon.

Sales of range oil in the United States, 1939-41, by States <sup>1</sup>
[Thousands of barrels]

			19	41
State	1939	1940	Total	Percent of total
Massachusetts New York Connecticut New Jersey Rhode Island Illinois Maine Pennsylvania New Hampshire Michigan Minnesota North Carolina Vermont Florida Wisconsin Maryland Missouri	2, 172 1, 387 1, 328 698 781 479 403 532 468 439 446 492	13, 419 7, 613 3, 921 3, 556 2, 619 1, 733 1, 704 920 898 620 555 577 560 542 516 531 485 398	13, 187 7, 711 3, 963 3, 626 2, 495 2, 185 1, 827 949 907 712 670 667 638 628 616 518 477 457	28.6 16.7 5.6 4.7 2.1 2.1 1.4 1.4 1.5 1.1
Owa. Pexas ndiana	291 304 202 214 2, 333	335 325 272 234 2, 359	456 416 355 324 2, 326	1.
Total United States	37, 061	44, 692	46, 110	100.

<sup>&</sup>lt;sup>1</sup> Figures for 1942 by States not yet available.

### FUEL OIL

An anticipated large increase in the domestic demand for fuel oils in 1942 was not realized. Rationing of fuel oil in the East coast and Pacific Northwest in 1942, which became necessary because of trans-

portation difficulties and military needs, reduced deliveries to a level The fuel-oil supply in 1941 (produclittle above 1941 requirements. tion plus imports and transfers from crude) was not only sufficient to cover the domestic demand and export trade, but there was also a surplus to add to stocks. The whole situation was changed in 1942, when imports of fuel oil dropped to half the 1941 quantity and as a result a heavy draft on stocks was made to cover this loss.

The record-breaking fuel-oil requirements of recent years continued into 1942, even though rationing, transportation difficulties, and conversions to other fuels by important consumers all tended to lower The indicated domestic demand for fuel oils in 1942— 587,785,000 barrels—was 6 percent above the 1941 total—556,246,000 The domestic market for distillate fuel oils increased from 172,824,000 barrels in 1941 to 184,312,000 barrels in 1942 and for residual grades from 383,422,000 barrels in 1941 to 403,473,000 in 1942. It is noted that the respective percentage gains in domestic demand for distillate fuel oils (7 percent) and residuals (5 percent) were about the same in 1942 as in 1941. These percentage increases are quite different from those in 1940, when an unusual cold spell in the first quarter forced up the requirements for distillates (domestic heating oils) to a 19-percent gain for the year compared with a 5-percent nominal increase for residual grades, and in 1941, when the larger gain (13 percent) was in residual fuel oils, reflecting the demand for fuel by expanding war industries, contrasted with only a 7-percent increase in requirements for distillate grades.

Salient statistics of fuel oil in the United States, 1941-42 [Thousands of barrels]

		1941	•		1942 1	
	Distillate fuel oil	Residual fuel oil	Total	Distillate fuel oil	Residual fuel oil	Total
Stocks at beginning of year: Refinery Bulk terminal Production	32, 082 10, 829 189, 177	83, 548 4, 478 342, 367	115, 630 15, 307 531, 544	<sup>2</sup> 36, 322 <sup>2</sup> 13, 008 196, 714	<sup>2</sup> 68, 727 <sup>2</sup> 14, 232 358, 901	<sup>2</sup> 105, 049 <sup>2</sup> 27, 240 555, 615
Transfers from crude oil to fuel oil: California East of California Imports Exports		8, 874 4, 095 37, 369 14, 114	9, 004 6, 478 42, 443 31, 039	12 2, 484 3, 428 22, 716	14, 658 4, 625 17, 645 13, 532	14, 670 7, 109 21, 073 36, 248
Stocks at end of year:  Refinery Bulk terminal	38, 895 11, 031	78, 054 5, 141	116, 949 16, 172	32, 659 12, 281	49, 961 11, 822	82, 62 24, 10
Indicated domestic demand: Class I railroads, purchases 3 Public-utility power plants 5 All other demands	(4) (4) (4)	(4) (4) (4)	83, 609 20, 248 452, 389	(4) (4) (4)	(4) (4) (4)	104, 07 15, 30 468, 41
	172, 824	383, 422	556, 246	184, 312	403, 473	587, 78

A review of domestic demand statistics for distillate fuel oil, by quarters, reveals an 11-percent increase in the first 3 months, due largely to the requirements for domestic heating oils, as January and February 1942 were considerably colder than the same months in 1941. The percentage gain in the first quarter of 1942 would have been even greater had not mild weather in March reduced the requirements for

Subject to revision.
 Stocks on new basis.
 Interstate Commerce Commission; total includes Diesel fuel.

Figures not available.
Federal Power Commission.

that month by 1.3 million barrels and lowered the quarterly demand correspondingly. There was a nominal gain of 5 percent in the domestic market for distillates in the second quarter of 1942, followed by a 1-percent decline in the third quarter compared with similar periods of 1941. The drop in the third quarter of 1942 was directly connected with the order preventing the delivery of fuel oil for heating or cooling purposes in District 1 (17 East Coast States and the District of Columbia) during the period August 3-September 15. Deliveries of distillate fuel oil gained 7 percent in the final quarter of 1942, compared with the same period of 1941, even with coupon rationing of light heating oils, which became effective October 1, 1942.

Larger percentage gains (13 percent in the first quarter and 6 percent in the second quarter compared with the respective periods of 1941) were realized in the domestic demand for residual fuel oils than for distillate grades, reflecting the rapidly growing industrial expansion connected with the all-out war program. Restricted deliveries in the July-September period 1942 are evident in the slight loss when the demand is compared with the 1941 market in the same months. There was only a 2-percent gain in domestic demand for heavy fuel oils in the final quarter of 1942 over the 1941 quarter, as many important users of liquid fuel had by that time converted to coal or other sources

of energy.




FIGURE 11.—Sales of fuel oil and range oil in the United States, 1932-41, by uses.

At present, with the Bureau's annual survey of fuel-oil sales incomplete, little is known about the distribution of fuel oil by principal uses in 1942. Preliminary monthly statistics released by the Interstate Commerce Commission give total railroad purchases of 104,-072,000 barrels in 1942, a 24-percent gain over 1941 requirements of 83,609,000 barrels. Records of the Bureau of Foreign and Domestic Commerce, United States Department of Commerce, show 25,148,000 barrels of bunker fuel oil delivered to vessels engaged in foreign trade in 1942—a decrease of 11 percent below the 1941 total of 28,-337,000 barrels. Many power plants that formerly used fuel oil for producing electric energy converted to coal or other fuels in 1942; this cooperation in the national emergency resulted in considerable saving of fuel oil, the total consumption declining from 20,248,000 barrels in 1941 to 15,300,000 in 1942, a drop of 24 percent. Rationing, temporary stoppages of deliveries, conversions to other fuels, and shortage of spot supplies were factors that probably reduced the consumption of fuel oil by smelters, mines, and manufacturing industries, by oil companies, and in space heating in 1942 compared with 1941.

Figure 11 shows graphically the distribution of fuel-oil sales by

principal uses for 1932-41. The volume of yearly sales for each principal use, as indicated by the different columns, is based upon totals derived from the annual fuel-oil survey of the Bureau. Distillate fuel oil, residual fuel oil, and kerosine sold as range oil are

included.

Sales of fuel oil 1 and of range oil in the United States, 1937-41, by uses 2 [Thousands of barrels]

Use	1937	1938	1939	1940	1941
Fuel oil: Railroads. Ships' bunkers (including tankers) Gas and electric power plants Smelters and mines. Manufacturing industries Heating oils. Fuel oil (No. 1) sold as range oil. Oil company fuel. All other uses.	69, 458 84, 990 26, 510 74, 798 116, 617 2, 747 42, 924 23, 759	57, 829 74, 266 27, 567 60, 038 118, 323 2, 902 43, 517 23, 408	63, 235 79, 254 32, 039 67, 043 136, 232 3, 220 49, 045 26, 875	68, 098 74, 803 32, 795 73, 940 160, 379 3, 977 51, 928 32, 838	85, 510 67, 635 38, 774 88, 387 167, 514 4, 449 55, 297 46, 763
Total United States_ Exports and shipments to noncontiguous Terri- tories Total Range oil	441, 803 45, 433 487, 236 32, 259	407, 850 47, 561 455, 411 33, 707	456, 943 49, 505 506, 448 37, 061	498, 758 35, 249 534, 007 44, 692	554, 329 31, 039 585, 368 46, 110

Includes distillate fuel oil, residual fuel oil, and some crude oil burned as fuel.
 Figures for 1942 not yet available.

Sales of distillate fuel oil 1 in the United States, 1937-41, by uses 2 [Thousands of barrels]

Use	1937	1938	1939	1940	1941
Railroads. Ships' bunkers (including tankers). Gas and electric power plants Smelters, mines, and manufacturing industries. Heating oils. Fuel oil (No. 1) sold as range oil Oil company fuel. All other uses.	1, 629	1, 720	2, 258	3, 194	4, 948
	13, 494	13, 088	14, 108	13, 249	10, 957
	2, 989	3, 685	4, 131	4, 561	5, 152
	5, 691	5, 224	6, 192	7, 330	10, 363
	81, 235	82, 388	97, 131	115, 533	120, 908
	2, 747	2, 902	3, 220	3, 977	4, 449
	803	939	804	1, 064	1, 116
	8, 056	7, 495	10, 726	11, 744	15, 449
Total United StatesExports and shipments to noncontiguous Territories	116, 644	117, 441	138, 570	160, 652	173, 339
	30, 129	29, 641	32, 020	19, 140	16, 925
Total	146, 773	147, 082	170, 590	179, 792	190, 264

<sup>&</sup>lt;sup>1</sup> Includes Diesel fuel.
<sup>2</sup> Figures for 1942 not yet available.

The state of the s

### Sales of residual fuel oil in the United States, 1937-41, by uses 2

#### [Thousands of barrels]

Use	1937	1938	1939	1940	1941
Railroads. Ships' bunkers (including tankers). Gas and electric power plants Smelters, mines, and manufacturing industries. Heating oils. Oil company fuel. All other uses.	67, 829	56, 109	60, 977	64, 904	80, 565
	71, 496	61, 178	65, 146	61, 554	56, 678
	23, 521	23, 882	27, 908	28, 234	33, 622
	69, 107	54, 814	60, 851	66, 610	78, 024
	35, 382	35, 935	39, 101	44, 846	46, 606
	42, 121	42, 578	48, 241	50, 864	54, 181
	15, 703	15, 913	16, 149	21, 094	31, 314
Total United States	325, 159	290, 409	318, 373	338, 106	380, 990
Exports and shipments to noncontiguous Territories _	15, 304	17, 920	17, 485	16, 109	14, 114
Total	340, 463	308, 329	335, 858	354, 215	395, 104

Includes Navy grade and crude oil burned as fuel.
 Figures for 1942 not yet available.

The overseas market for fuel oil made a net gain in 1942 over 1941, as a large increase in distillate exports was partly counteracted by a loss for residual grades. Total exports of fuel oil (including shipments to noncontiguous Territories of the United States) was 36,248,000 barrels in 1942, a gain of 17 percent over the 1941 total of 31,039,000 barrels. The foreign demand for distillates increased from 16,925,000 barrels in 1941 to 22,716,000 in 1942, a gain of 34 percent, while the market for residuals (totaling 13,532,000 barrels in 1942) was lower by 4 percent than the 1941 quantity of 14,114,000 barrels.

Greatly increased exports of fuel oil went to the United Kingdom and its Dependencies through Lend-Lease arrangements in 1942. Exports of distillate fuel oil to the United Kingdom increased from 7.158,000 barrels in 1941 to 15,714,000 in 1942 and to Canada from 394,000 barrels in 1941 to 493,000 in 1942, while shipments to Australia of 1,002,000 barrels and to New Zealand of 855,000 barrels in 1942 compared with trivial quantities to those countries of the British Empire in 1941. In other words, an export trade in distillate fuel oil, which formerly favored Japan (3,348,000 barrels in 1941) was shifted to our British allies in the South Pacific.

The export market for residual grades of fuel oil was also changed Japan and the Philippines were cut off entirely; and unusually large shipments to Chile in 1941 (2,294,000 barrels) slumped to 52,000 barrels in 1942, largely because of the lack of tankers. Exports of residual fuel oil to the United Kingdom increased from 1,542,000

barrels in 1941 to 2,696,000 in 1942.

The production of fuel oil increased 5 percent-from 531,544,000 barrels in 1941 to 555,615,000 in 1942. The gain must be attributed entirely to an increased percentage yield (41.6 percent in 1942 compared with 37.7 percent in 1941), as crude runs to stills were lower by 5 percent in 1942 than in 1941. Unusual conditions prevailing in 1942 enabled refiners to expand the yield of fuel oil to the extent indicated, as motor gasoline was not wanted to the limit of the crude content because of rationing on the East coast (to save gasoline and rubber tires) dating from May 17, 1942, and for the entire country (to save rubber tires) from December 1, 1942. Consequently producers adjusted their runs to make less motor fuel and more of the demand product—fuel oil.

Sales of fuel oil 1 in the United States, 1937-41, by regions and States 2
[Thousands of barrels]

Region and State	1937	1938	1939	1940	1941
Pacific Coast:					
	0-0		2.22		1.0
Washington	11, 352	9, 241	9, 193	9, 688	12, 199
Oregon.	10,879	9, 308	8, 752	11,089	12, 56
California	70, 952	59, 316	69, 790	71, 516	77, 20
Arizona	3, 994	2, 838	2, 220	3, 693	4, 43
Nevada	3, 790	2,690	3, 109	3, 418	
	0, 100	2,000	0, 109	0, 418	4, 286
Idaho	520	400	400		1 - 1 - 1 <u></u> 1
Montana		420	483	565	75
Montana	1,802	1, 451	1,947	2,077	3, 22
Wyoming	1, 799	1,654	1,853	2,012	2, 26
Utah	508	471	485	603	69
Colorado	644	636	880	1,097	1. 47
New Mexico	561	502	557	630	70
North Central:	001	002	001	000	70.
North Dakota	410	440			
Courth Doboto	416	442	594	647	677
South Dakota	613	777	891	891	90
Minnesota	5, 184	4, 974	5, 909	6, 939	7, 30
Nebraska	1,955	1, 982	2, 483	2, 721	2, 76
10W8	2 261	2, 325	2, 969	3, 449	3, 99
Wisconsin	4, 823	4,748	5, 793		0, 990
Illinois	20, 964	10,020		6, 885	7, 34
Indiana		19, 930	22, 561	26, 182	28, 94
Indiana	7, 905	7,824	8, 977	9,965	12, 78
Michigan	9,847	8, 228	10, 119	11, 967	13, 58
Ohio	8,030	7, 105	8, 161	9,084	10.97
Kentucky	973	840	1, 110	1, 355	1, 69
Tennessee.	593	557	695	1,045	1, 26
South Central:	0.00	007	000	1,040	1,200
Missouri	0.000	0.500	0.000		
Vorge	8, 980	8, 502	9, 339	10, 404	10, 948
Kansas	7, 364	6, 687	7, 605	8, 162	9, 277
Texas	43, 231	37, 672	42,012	43, 222	51, 634
Oklahoma	9.083	8, 269	8, 112	8, 544	9, 303
Arkansas	2,658	2,056	2, 156	2, 562	3, 136
Louisiana	12, 350	10, 871	11, 318	11,810	17, 15
Mississippi	796	529	631		
Alabama				619	999
New England:	1,889	2, 113	2, 127	1,976	2,780
Maine	2, 490	2, 150	2,645	3,040	3, 892
New Hampshire	1, 513	1, 431	1.812	2, 153	2, 568
Vermont	566	539	675	803	901
Massachusetts	21, 798	21, 362	24, 392	26, 857	29, 996
Rhode Island	7, 283	6, 839	7, 893	8,839	
Connecticut	7, 822				9, 594
Middle Atlantic:	1,022	7, 482	9,064	10,675	11, 358
Mary Vanh					
New York	43, 428	43, 389	48, 154	54, 520	56, 780
New Jersey	44, 232	42,862	48, 087	49, 578	47, 904
Pennsylvania	26, 320	26, 213	27, 285	29, 269	31, 479
Delaware	1,666	1,400	1, 596	1,717	1. 80
Maryland	9, 549	9, 003	10,000	10,000	
Maryland District of Columbia			10, 218	12, 286	13, 436
Posth Atlantice	2, 108	2, 137	2, 541	2, 986	3, 459
South Atlantic:			1		
Virginia	3, 638	4, 824	4, 539	4, 794	4. 46
West Virginia	807	912	1,046	1, 128	1, 261
North Carolina	591	699	930	1, 112	1. 384
South Carolina	679	757	1, 109		
Georgia				1, 253	1, 40
Florida.	1,787	2,022	2, 288	2, 418	2, 958
_	8,810	8, 871	9,838	10, 513	12, 445
Total United States	441, 803	407, 850	456, 943	498, 758	554, 329

Includes distillate fuel oil, residual fuel oil, and some crude oil burned as fuel.
 Figures for 1942 not yet available.

The output of distillate fuel oil, the larger share of which is used for space heating, increased by 4 percent—from 189,177,000 barrels in 1941 to 196,714,000 in 1942. The yield of light fuel oil moved up from 13.4 percent in 1941 to 14.7 percent in 1942. The production of residual fuel oil, in great demand in 1942 because of expanded industrial activities in connection with the war, increased 5 percent—from 342,367,000 barrels in 1941 to 358,901,000 in 1942—and the upward shift in percentage yield (26.9 percent in 1942 compared with 24.3 percent in 1941) was even greater than in the case of light fuel oil.

Production of distillate fuel oil increased in all refinery districts except the East Coast and California. The inability to obtain domestic or foreign crude to full requirements on the East coast in 1942, because of transportation difficulties, forced down crude runs materially (161,142,000 barrels in 1942 compared with 217,046,000 in 1941); consequently, there was a decline in the production of distillate fuel oil from 40,827,000 barrels in 1941 to 31,132,000 in 1942, a 24-percent shrinkage. The percentage yield of distillate was stepped up slightly (18.8 percent in 1941 and 19.3 percent in 1942), but this adjustment added very little to the distillate output, considering the much smaller volume of crude processed in 1942. The production of distillate fuel oil in the California district declined from 27,803,000 barrels in 1941 to 24,398,000 in 1942. Although crude runs to stills increased in California in 1942, the percentage yield of distillate was reduced materially (13.0 percent in 1941 and 10.6 percent in 1942) to increase the output of residual grades, which were in great demand. The production of distillate fuel oil increased considerably in the Appalachian, Indiana-Illinois, Oklahoma-Kansas, Texas Inland, Arkansas and Louisiana Inland, and Rocky Mountain districts, all areas either of high consumption, or areas where rail shipment of light fuel oil could be made to important markets to the north and Percentage gains in the output of distillate fuel oil were not so high in the Texas and Louisiana Gulf districts, because of the disrupted tanker traffic and the resulting inability to make normal shipments to East coast consuming centers.

Production of residual fuel oil declined in 4 of the 10 refinery districts in 1942 even though the national total was up 5 percent for the A 9-percent drop (45,653,000 barrels in 1942 compared with 50,113,000 in 1941) in the output of residuals in the East Coast district was the result of lower crude runs to stills, which even a much higher percentage yield of 28.3 percent in 1942 over 23.1 percent in 1941 could not fully overcome. The production of heavy fuel oils in 1942 was considerably less in the Texas Gulf district, a source of residual fuel oil second only to California in importance, because of a 16percent decline in runs to stills, an adverse factor that was only partly offset by a slightly higher percentage yield (23.3 percent in 1941 and 24.4 percent in 1942). Lack of an active market for residual fuel oils, lower crude runs, and smaller percentage yields were all reflected in a declining production of heavy fuel oils in the Louisiana Gulf and Arkansas and Louisiana Inland districts in 1942 compared with 1941. Large percentage gains in residual fuel-oil production were realized in the Indiana-Illinois, Oklahoma-Kansas, and Texas Inland districts in 1942, as the fuel oil could be rail-shipped to consumers. High gains in residual output were likewise made in the Appalachian and Rocky Mountain districts, but the quantities produced were relatively unim-An 18-percent gain in residual fuel-oil production in California in 1942 (104,255,000 barrels in 1942 compared with 88,411,000 in 1941) was not sufficient to satisfy a very active demand, and the balance was supplied from storage and increased transfers from the

crude account.

Some crude oils, of little value for refining, are burned directly as Such crudes are termed "transfers," being changed from the crude to the fuel-oil account on oil-company books. Transfers of fuel oil increased from 15,482,000 barrels in 1941 to 21,779,000 in 1942, a gain of 40 percent. Practically all this increase was limited to residual grades transferred in California (14,658,000 barrels in 1942 compared with 8,874,000 in 1941) where there was a very active market for heavy fuel oils in 1942. Transfers of heavy crudes for areas east of California increased but slightly from 4,095,000 barrels in 1941 to 4,625,000 in 1942. The lower-gravity crudes covered in the above totals, both for California and east of California, are consumed as fuel on leases and in industrial plants. Some light-gravity crudes are used by pipe lines as fuel and are classified as "transfers" to the distillate fuel-oil account in the Bureau's petroleum statistics. Transfers of light crudes were insignificant in California both in 1941 and 1942; however, east of California these transfers increased from 2,383,000 barrels in 1941 to 2,484,000 in 1942.

Disrupted tanker traffic due to sinkings and shifts of boats to military use was reflected in the sharp drop in imports of fuel oils in 1942. Receipts of these products from foreign sources dropped 50 percent—from 42,443,000 barrels in 1941 to 21,073,000 in 1942. In other words, imported fuel oil supplied 8 percent of the domestic demand in 1941 compared with only 4 percent in 1942. The decline in imports of residual fuel oils was more pronounced than for the lighter grades. Receipts of heavy fuel oils from abroad were down by 53 percent from 37,369,000 barrels in 1941 to 17,645,000 in 1942, while distillate imports of 3,428,000 barrels in 1942 were 32 percent below the 1941 total

of 5,074,000 barrels.

The large reduction of 26,000,000 barrels in year-end fuel-oil stocks in 1942 compared with 1941 was partly attributable to greatly reduced imports in 1942. In other words, supplies to meet the demand were taken from storage to offset diminishing receipts from foreign sources. Fuel-oil stocks reported for the end of 1942 (106,723,000 barrels) were 19 percent below the total of 132,289,000 barrels for the same period of 1941. The greater part of fuel-oil stocks (79 percent of the 1941 total and 77 percent of the 1942 total) was held at refineries, where year-end inventories decreased by 21 percent—from 105,049,000 barrels in 1941 to 82,620,000 in 1942. Fuel oil held at bulk terminal points decreased by 12 percent—from 27,240,000 barrels in 1941 to 24,103,000 in 1942—and furthermore constituted 23 percent of the 1942 final inventory compared with 21 percent in 1941.

Reviewing light and heavy fuel-oil stocks separately, it is noticed that the shrinkage in volume in 1942 was far more critical in residual grades that for distillates. Heavy fuel oils held at the end of 1942, totaling 61,783,000 barrels, were 26 percent below the comparative 1941 quantity of 82,959,000 barrels, while light fuel oils dropped by only 9 percent—from 49,330,000 barrels in 1941 to a final total of 44,940,000 in 1942. Both light and heavy fuel-oil stocks at refineries and at bulk terminals showed marked declines in 1942 compared with 1941. Refinery stocks of residual fuel oils declined by 27 percent—from 68,727,000 barrels in 1941 to 49,961,000 at the close of 1942—while a 10-percent drop was recorded for distillate grades from 36,322,000 barrels in 1941 to 32,659,000 in 1942. Residuals at refineries made up 83 percent of the total heavy fuel-oil stocks at the

	D		371-13 (-			Tran	sfers 1		Towns	onto	Trum	orts		nestic	Stoc	ulze
Month and district	Produ	1011011	Yield (1	percent)	East of	f Calif.	Calif	ornia	Imp	orts	Exp		den	nand		
	1941	1942 2	1941	1942 ²	1941	1942 ²	1941	1942 2	1941	1942 2	1941	1942 2	1941	1942 2	1941	1942 2
By months: January February March April May June July August September October November December	16.024	16, 902 15, 194 16, 214 14, 002 13, 436 15, 210 16, 149 17, 052 18, 062 18, 858 17, 562 18, 073	15. 4 14. 7 13. 9 13. 2 13. 0 12. 7 13. 0 12. 4 13. 2 13. 1 13. 4 13. 7	14. 2 14. 4 14. 7 13. 4 12. 6 14. 4 14. 5 15. 9 16. 2 15. 6 16. 0	176 172 182 172 195 200 201 221 216 222 216	225 178 186 185 200 188 206 213 217 227 215 244	5 51 44 1 12 10 4	2 1 2 7	421 483 277 195 300 211 626 463 814 656 340 288	403 369 407 92 195 54 40 142 125 421 647 533	1, 595 791 1, 028 876 1, 156 1, 380 1, 161 2, 300 1, 283 1, 703 1, 445 2, 207	1,080 1,160 1,797 1,925 1,151 2,052 4,180 1,569 1,705 2,572 1,516 2,009	21, 010 17, 783 19, 847 12, 264 11, 233 10, 853 10, 653 9, 667 11, 516 11, 752 15, 659 20, 587	24, 981 21, 671 18, 517 13, 769 11, 191 11, 187 6, 987 10, 649 13, 800 13, 050 15, 900 22, 610	37, 926 34, 790 29, 805 31, 725 35, 389 38, 274 43, 037 47, 163 51, 412 55, 385 55, 073 49, 926	40, 801 33, 711 30, 205 28, 792 30, 281 32, 501 37, 729 42, 918 45, 817 49, 701 50, 709 44, 940
Total United States	189, 177	196, 714	13. 4	14.7	2, 383	2, 484	130	12	5, 074	3, 428	16, 925	22, 716	172, 824	184, 312	$\left\{\begin{smallmatrix} 49,926\\ 349,330\end{smallmatrix}\right.$	44, 940
By districts: East Coast	2, 430 59, 591 8, 631 2, 535	31, 132 6, 769 34, 388 18, 344 3, 664 60, 697 9, 428 4, 112 3, 782 24, 398	18.8 9.1 10.5 10.6 3.6 16.4 45.9 8.6 8.3 13.0	19.3 11.8 13.0 14.2 5.4 19.8 17.7 14.4 11.0	503 699 718 234 97 13 119	552 861 658 186 98 38 91	130	12	(4)	(4)	(4)	(4)	(4)	(4)	18, 035 704 5, 552 1, 766 301 7, 801 1, 798 341 319 12, 713	8, 415 860 5, 783 2, 155 331 12, 336 1, 671 826 378 12, 185
Total United States	189, 177	196, 714	13. 4	14.7	2, 383	2, 484	130	12	5, 074	3, 428	16, 925	22, 716	172, 824	184, 312	<sup>3</sup> 49, 330	44, 940

Figures represent crude oil used as fuel on pipe lines.
 Subject to revision.
 New basis to compare with 1942.
 Figures not available.

## Comparative analyses of statistics for residual fuel oil in the United States, 1941-42, by months and districts [Thousands of barrels]

						Tra	nsfers 1									
Month and district	Prod	uction	Yield (1	percent)		of Cali- nia	Cali	ornia	Imp	orts	Exp	orts		nestic nand -	Stoo	eks
	1941	1942 2	1941	1942 2	1941	1942 2	1941	1942 2	1941	1942 2	1941	1942 2	1941	1942 2	1941	1942 2
By months: January. February. March. April. May. June. July. Angust. September. October. November. December.	26, 748 27, 994 27, 882 28, 624	29, 405 27, 254 28, 095 29, 440 30, 971 28, 352 30, 096 30, 446 30, 402 31, 239 31, 311 31, 890	25. 2 25. 8 24. 9 24. 0 23. 4 24. 0 23. 1 24. 3 24. 3 24. 4	24. 7 25. 8 25. 4 28. 1 29. 0 26. 9 27. 9 26. 8 26. 9 27. 9 28. 1	299 277 294 327 360 281 277 323 394 394 452 417	589 450 304 361 366 360 369 354 427 391 348	495 560 366 193 561 789 667 507 1,758 1,086 982 910	1,041 1,060 1,309 1,465 1,638 1,274 1,079 1,025 1,617 1,068 1,116 966	2, 279 2, 651 4, 191 2, 968 2, 474 2, 458 1, 488 1, 564 4, 327 2, 469 3, 952 5, 548	3, 357 3, 297 2, 724 1, 483 539 342 521 626 476 1, 838 1, 230 1, 212	1,002 975 1,170 1,378 981 1,267 954 1,600 1,282 1,213 1,368 924	1, 264 786 917 1, 080 1, 370 1, 311 1, 358 1, 158 756 1, 133 881 1, 518	32, 885 30, 647 32, 626 31, 354 30, 328 29, 413 29, 290 30, 122 31, 831 32, 399 34, 914 37, 613	37, 701 34, 275 36, 803 34, 109 31, 414 31, 040 30, 104 30, 600 30, 442 33, 830 35, 376 37, 779	85, 092 82, 902 81, 634 79, 138 79, 218 79, 948 80, 760 82, 268 83, 752 84, 960 83, 730 83, 195	78, 386 75, 386 70, 098 67, 658 68, 388 66, 341 66, 935 67, 613 69, 264 68, 873 66, 664 61, 783
Total United States	342, 367	358, 901	24.3	26. 9	4, 995	4, 625	8, 874	14, 658	37, 369	17,645	14, 114	13, 532	383, 422	403, 473	83, 195 3 82, 959	61, 783
By districts: East Coast Appalachian Indiana, Illinois, Kentucky, etc. Oklahoma, Kansas, and Missouri Texas Inland Texas Gulf Coast Louisiana Gulf Coast Arkansas and Louisiana Inland Rocky Mountain California	14, 280 84, 806 13, 070 7, 180 7, 629 88, 411	45, 653 9, 498 55, 545 24, 788 16, 586 74, 778 11, 772 6, 734 9, 292 104, 255	23. 1 14. 4 18. 6 17. 6 21. 4 23. 3 24. 1 24. 5 22. 7 41. 5	28. 3 16. 5 21. 0 19. 2 24. 3 24. 4 22. 1 23. 5 27. 0 45. 3	739 283 429 747 945 622 330	689 278 602 1, 174 897 720 265	8, 874	14, 658	(4)	(4)	(4)	(4)	(4)	(4)	9, 805 578 4, 152 2, 046 1, 349 8, 710 2, 217 368 535 53, 199	3, 613 579 2, 446 1, 332 761 6, 275 1, 714 183 649 44, 231
Total United States	342, 367	358, 901	24. 3	26. 9	4, 095	4, 625	8, 874	14, 658	37, 369	17, 645	14, 114	13, 532	383, 422	403, 473	3 82, 959	61, 783

Represents quantities used on leases and for general industrial purposes.
 Subject to revision.
 New basis to compare with 1941.
 Figures not available.

close of 1941, compared with 81 percent of the 1942 quantity. Distillates at bulk terminals constituted 26 percent of the 1941 inventory and 27 percent in 1942, while residual grades carried at such terminals accounted for 17 percent of the heavy fuel-oil storage in 1941 and 19

percent in 1942.

Statistics for fuel-oil stocks show major declines in 1942 for both distillate and residual grades in the East Coast refinery district and also considerable loss for residuals in the California refinery area. Oil d stributors along the Atlantic seaboard, being unable to obtain adequate supplies of fuel oil in 1942 from the Gulf coast and inland areas by tanker, rail, or pipe line, were forced to make an unusual draft on locally held stocks. Over half of the distillate inventory (18,035,000 barrels at the end of 1941 dropped to 8,415,000 during 1942) and twothirds of the residual supply (9,805,000 barrels in 1941 and 3,613,000 n 1942) were liquidated in 1942. The largest share of residual fuel oils held nationally is stored in California, and there the quantities declined from 53,199,000 barrels at the close of 1941 to 44,231,000 in 1942, a 17-percent shrinkage. The 10-percent drop in distillate stocks in 1942 was a net loss, as outside of the major liquidation in the East Coast and slight declines in the Louisiana Gulf and California refinery districts all other areas showed gains in inventory for the year-a reflection of the lack of normal movement of supplies to markets to the north and east. The principal stock increase for distillates in 1942 was realized in the Texas Gulf district, where the volume rose from 7,801,000 barrels in 1941 to 12,336,000 at the end of 1942, or by 58 percent. Here the tanker shortage prevented an uninterrupted flow of light fuels to the East coast. The decline in heavy fuel-oil stocks most serious in the East coast and California areas, was general for all refinery districts of the country in 1942, except for static supplies in the Appalachian section and a 21-percent gain in the Rocky Mountain States; both regions are unimportant storage areas. Declines in inventory for residual fuel oil in 1942 ranged from a 23-percent reduction in the Louisiana Gulf to a 50-percent drop in the Arkansas and Louisiana inland district.

Tanker shipments of fuel oils from California to the East coast have dwindled sharply under war conditions, and although 203,000 barrels of distillates were shipped in 1941, no movements of fuel oils over this route were reported in 1942. The California refinery district (California, Oregon, Washington, Arizona, and Nevada) makes some overland rail and truck shipments of fuel oils to adjoining States. Distillates in this movement increased from 382,000 barrels in 1941 to 423,000 in 1942, while the volume of residuals handled continued the downward trend of recent years from 130,000 barrels in 1941 to 49,000

in 1942.

Sinkings and diversions of boats for military use in 1942 greatly disrupted the normal flow of fuel oils by tankers from the Gulf coast refinery districts to East Coast markets. The seriousness of this situation is evident when it is noted that the tanker movement (118,543,000 barrels of fuel oil in 1941) dropped to 43,660,000 barrels in 1942—a loss of 63 percent. Gulf tanker shipments of both light and heavy fuel oils to the Atlantic seaboard were down sharply in 1942, movements of distillates declining by 52 percent from 42,620,000 barrels in 1941 to 20,305,000 in 1942, and the traffic in residual grades

slumped from 75,923,000 barrels in 1941 to 23,355,000 in 1942—a loss

of 69 percent.

With the usual tanker movement of fuel oil from the Gulf coast to Eastern States at a low ebb in 1942, every effort was made to ship needed supplies into the Atlantic area by other means, such as tank cars, barges, and pipe lines. The railroads carried most of this rerouted traffic, hauling 8,329,000 barrels of distillate and 14,740,000 of residual from District 2 to District 1 and 18,951,000 barrels of distillate and 23,058,000 of residual fuel oil from District 3 to District 1 in 1942. Fuel oil moved by barge from the Gulf coast to Mississippi River points, totaling 1,811,000 barrels of light fuel oil and 937,000 of residual grades; possibly some of this oil plus quantities originating in District 2 reached Northern States in District 1 through the Ohio River system for a total of 192,000 barrels of distillate and 230,000 of residual fuel. Tankers and barges operating on the Great Lakes carried 2,344,000 barrels of light grades and 2,233,000 of heavy fuel oils to Eastern States in 1942. Barges following the Gulf coast supplement the fuel-oil supply in the Florida west coast by 655,000 barrels of distillate and 339,000 of residual grades in 1942. Pipe-line deliveries of fuel oil into District 1 appeared in 1942, the quantity being reported as 443,000 barrels of light oils.

Tanker rates on light and heavy fuel oil on the Gulf coast—North Atlantic (not east of New York) route were much higher in 1942 than in 1941, owing to surcharges permitted first by the Maritime Commission and later by the War Shipping Administration "to cover wartime operating expenses." The freight rate on No. 2 fuel oil—57 cents a barrel for November 1941—was dropped to 42 cents a barrel on January 19, 1942. This basic rate held throughout 1942; however, on February 23 the Maritime Commission allowed a surcharge of 37½ percent a barrel to be added to the established rate. The War Shipping Administration advanced the surcharge to 200 percent on April 6, and this charge held for the balance of the year. The Gulf coast—North Atlantic tanker rate for crude and heavy fuel oil (10°-19.9° gravity)—57 cents a barrel for November 1941—was dropped to 48 cents a barrel on January 19, 1942. The surcharges of 37½ percent and 200 percent allowed, respectively, by the Maritime Commission and War Shipping Administration for light fuel oil were likewise granted to tankers for carrying heavy fuel oil on this route.

Representative fuel-oil prices did not change greatly in 1942 compared with 1941, except where higher tanker rates had to be absorbed. The quotation for No. 2 straw fuel oil at refineries in Oklahoma averaged 3.82 cents a gallon in 1942 compared with 3.69 cents in 1941, and important mark-ups were seen in oils for ships' bunkers at New York where tanker rates were involved, Bunker C advancing from an average of \$1.34 a barrel in 1941 to \$1.61 in 1942 and Diesel grade going from \$1.99 a barrel to \$2.57. Bunker C at Gulf ports at 89 cents a barrel in 1942 varied little from the 1941 average quotation of 87 cents a barrel; however, Diesel oil for bunkers in this area rose by 8 cents in 1942 to \$1.64 average per barrel. An active market for heavy fuel oils in California in 1942 was shown in a 5-cent increase to an average of 85 cents a barrel for Bunker C, but the price of Diesel fuel at \$1.41 a barrel was only 1 cent above the 1940 average.

An average price for No. 2 straw fuel oil at refineries in Oklahoma—3.88 cents a gallon for November 1941—prevailed through January

1942. There was a transitional price of 3.87 cents a gallon in February 1942, and this settled to 3.86 by March, which average quotation held until late in August. A lower average price of 3.74 cents a gallon was quoted for September and October, followed by a slight rise to 3.75 cents in November and a slump to 3.65 cents a gallon for the final month of 1942.

Monthly average prices of kerosine and fuel oils in the United States, 1941-42 1

	January	February	March	April	May	June	July	August	September	October	November	December	Average for year
1941						-							
41°-43° gravity w. w. kerosine at refineries, Oklahoma cents per gallon	4. 12	4. 13	4. 13	4. 24	4. 42	4. 56	4. 56	4. 56	4. 56	4. 56	4. 56	4. 56	4. 41
Kerosine, tank-wagon at Chi- cagocents per gallon_ No. 2 straw fuel oil at refineries,	10.00	10.00	10.00	10.00	10. 50	10. 30	10. 30	10. 30	10. 30	10. 30	10. 30	10. 30	10. 20
Oklahomacents per gallon Bunker C for ships:	3.68	3. 57	3. 50	3. 50	3. 53	3. 63	3. 63	3. 81	3. 81	3. 87	3. 88	3.88	3, 69
New York  dollars per barrel Gulf coast California Diesel oil for ships:	83	. 83	. 83	. 86	. 88	. 88	.90	1.39 .90 .88	.90	.90			.87
New York dollars per barrel Gulf coast do California do	1.60	1. 56	1.43	1.46	1.48	1.52	2.00 1.55 1.40	1, 55	1.55	1.62	1.73	1.73	1. 99 1. 56 1. 40
1942													
41°-43° gravity w. w. kerosine refiners, Oklahoma	4 50	4 50	4 45		4 44	4 44	4 44	4 44	1 11	4 44	4 44	1 11	4.46
cents per gallon Kerosine, tank-wagon at Chi- cagocents per gallon	1	10.00			100			1.0					10.30
No. 2 straw fuel oil at refineries, Oklahomacents per gallon Bunker C for ships: New York				1						F			3. 82
dollars per barrel Gulf coastdo Californiado Diesel oil for ships:	.90	.90	.90	. 90		. 90	.90	. 89	. 88	. 88	. 86	. 85	1. 61 . 89 . 85
New York  dollars per barrel  Gulf coast do  California do	1.73	1.73	1.64	1.62	1.62	1.62	3. 24 1. 62 1. 43	1, 62	1.62	1.62	1.02	1.00	2. 57 1. 64 1. 41

<sup>&</sup>lt;sup>1</sup> Platt's Oil Price Handbook.

The average price of Bunker C at New York dropped from \$1.41 a barrel in December 1941 to \$1.37 in January and \$1.35 in February 1942, indicating lower tanker rates on the Gulf Coast—North Atlantic route. Advancing tanker rates caused the Bunker C average price at New York to rise gradually to \$1.80 a barrel in May; this "high" held through July, after which the quotation for heavy bunkers settled to \$1.66 a barrel in August and to \$1.65 from September to the end of 1942. The average quotation for Bunker C at Gulf ports—90 cents a barrel for July 1941—remained through July 1942, when there was a gradual reduction to 89 cents in August, 88 cents in September and October, 86 cents in November, and finally 85 cents a barrel in December 1942. Bunker C in California sold for 88 cents a barrel average from June 1941 through May 1942, then dropped to 84 cents a barrel for the remaining months of the year.

The cost of Diesel fuel for bunkers at New York was responsive to rising Gulf-to-New York tanker rates. An average quotation of \$2.15 a barrel, starting in September 1941, prevailed through February 1942, when advancing tanker costs gradually pushed up the price to a "high" of \$3.24 a barrel in July 1942. August brought a drop to \$2.82 and then to \$2.78 for the final months of the year. The price of Diesel for bunkers at Gulf ports—\$1.73 a barrel in November 1941—was maintained through February 1942, when there was a drop to \$1.64 in March and to \$1.62 in April; this average quotation remained in force until December 1942, when the price rose to \$1.65 a barrel. Ships paid \$1.40 a barrel for Diesel fuel in California from July 1941 through May 1942, when there was an advance to \$1.43 a barrel; this higher quotation was maintained for the balance of the year.

The Bureau of Labor Statistics, United States Department of Labor, releases monthly data covering the retail prices of various fuels in many cities of the country. These publications show that the retail price of representative No. 2 domestic heating oil at Chicago—7.65 cents a gallon, effective in October 1941—was maintained at the same level throughout 1943. The consumer's price for No. 2 fuel oil at New York—7.27 cents a gallon ruling in November 1941—remained unchanged through March 1942. After this date rapidly rising freight costs for tanker and rail shipments pushed up the retail quotation of No. 2 to 9.99 cents a gallon in July. Price reductions on gasoline and fuel oils along the Atlantic coast, effective August 5, 1942, as ordered by the Office of Price Administration made possible by subsidies to dealers from the Defense Supplies Corporation to cover mounting transportation and other costs, forced down the retail cost of No. 2 fuel oil to 8.79 cents a gallon for the remaining months of the year.

#### LUBRICATING OIL

The fewer miles traveled by motor vehicles in 1942 because of tire and gasoline rationing and the restriction of speed to 35 miles per hour were shown by a decline in the domestic consumption of lubricants to 29,018,000 barrels compared with 30,255,000 used in 1941. Production decreased to 38,626,000 barrels from 39,539,000 in 1941, and exports were 8,311,000 barrels compared with 9,924,000 in 1941. Stocks increased to 9,424,000 barrels at the end of 1942 compared with 8,127,000 at the end of 1941.

Automotive use of lubricants dropped from 11,679,000 barrels in 1941 to 8,704,000 in 1942. This, principally, was attributable to the reduction in mileage traveled by passenger cars, but lower consumption of oil because of slower speeds was also a factor. A tendency contributing slightly in the opposite direction was the older average age of vehicles.

Consumption of lubricants for industrial uses rose to 20,314,000 barrels compared with 18,576,000 in 1941 and 13,760,000 in 1940. This gain indicates not only the rise in industrial activity and military requirements but also new uses for lubricating oils.

Comparative analyses of statistics for lubricating oil in the United States, 1941-42, by months and districts

	(thous	etion ands of rels)	Yie (perc	eld ent)	demand	estic l (thou- parrels)		cks ands of rels)
	1941	1942 1	1941	1942 1	1941	19424	1941	1942 1
By months:						0.400	0 000	
JanuaryFebruary	2, 943	3, 497	2.7	2.9	2, 367	2,680	8,809	8, 266
February	2, 522	3, 174	2.5	3.0	1,797	2, 453	8,790	8, 429
March	2, 813	3,533 3,438	2.5	3. 2	2, 263	2,615	8, 637 8, 363 7, 835	8, 470
Anril	3, 213	3,438	2.9	3.3	2,712	2, 781	8,363	8,470
Mav	3, 322	3,439	2.8	3, 2	2,889 3,171	2, 525	7,835	8,768
Tuna	3, 520	3,231	3.0	3.1	3, 171	2,665	7.353	8,75
MayJuneJuly	3, 563	3, 231 3, 133	2.9	2.8 2.7	3,055	1,962	7, 107 7, 206	8,94
August	3, 561	3, 141	2.9	2.7	2,562	2, 128	7,206	9,30
September		2, 951	2.8	2.6	2,636	2, 267	7, 415	9, 27
October		3, 057	2.8	2.6	2,656	2, 112	7,487	9,42
November	3, 607	2,983	3.0	2.7	2,496	2,598	7,752	9,33
December	3, 554	3,049	2.8	2.7	1,651	2, 232	8, 127	9,42
December	0,001	0,010						
Total United States	39, 539	38, 626	2.8	2.9	30, 255	29, 018	8, 127	9, 424
By districts:			$i_j = i_j - \chi^*$					0.550
East Coast	8,608	7,798	4.0	4.8	1		2,406	2, 579
Annalachian	6, 414	6,417	12.0	11.2			745	91:
Indiana, Illinois, Kentucky, etc. Oklahoma, Kansas, and Mis-	4, 307	4, 326	1.7	1.6			747	82
Oklahoma, Kansas, and Mis-								1 00
souri	3,976	4, 277	3.1	3.3			749	1,00
Toyes Inland	358	260	. 5	.4	(2)	(2)	126	7
Texas Gulf Coast	9,677	9, 356	2.7	3.0	l I	l	1,588	2,12
Louisiana Gulf Coast	2, 093	2,066	3.9	3.9	11		255	30
Arkenses and Louisiana Inland	679	1,220	2.3	4.3	11	ł	49	11
Rocky Mountain	187	234	.5	.7	[[	1	103	12
California	3, 240	2,672	1.5	1.2	)		1,359	1,37
Total United States	39, 539	38, 626	2.8	2.9	30, 255	29, 018	8, 127	9,42

<sup>1</sup> Subject to revision.

The Texas Gulf Coast district maintained the lead in production of lubricating oil, its 9,356,000 barrels being 24.2 percent of the total. The relative standing of the East Coast district continued its downward trend, declining to 20.2 percent from 21.8 in 1941. California dropped to 6.9 percent compared with 8.2 in 1941 and 9.1 in 1940, the year of its highest relative production. The Inland Louisiana-Arkansas district had the greatest increase in production—from 1.7 percent of the total in 1941 to 3.2 in 1942. The Oklahoma, Kansas, Missouri district followed, with an increase from 10.1 percent to 11.1.

Lubricating-oil stocks of 9,424,000 barrels at the end of 1942 were the highest for any year end since 1931. They increased in all of the districts except Texas Inland, the gain of 34 percent in the Texas Gulf Coast district being the largest.

Domestic demand for lubricating oil, 1938-42 [Thousands of barrels]

		Auton	notive			Total
Year	Passenger cars	Trucks	Busses	Total	Industrial	demand
1938	8, 195 8, 245 8, 390 9, 056 6, 162	2, 185 2, 298 2, 327 2, 398 2, 304	199 205 213 225 238	10, 579 10, 748 10, 930 11, 679 8, 704	10, 654 12, 965 13, 760 18, 576 20, 314	21, 233 23, 713 24, 690 30, 255 29, 018

<sup>1</sup> Subject to revision.

<sup>&</sup>lt;sup>2</sup> Figures not available.

### Automotive consumption of lubricants in the United States, 1941-42 1 [Thousands of barrels]

Use	Passen	ger cars	Tru	icks	Bu	sses
	1941	1942	1941	1942	1941	1942
Crankcase oil.  Transmission oils	8, 392 664	5, 650 512	2, 170 228	2, 084 220	190 35	200
Total lubricating oils	9, 056 598	6, 162 461	2, 398 114	2, 304 110	225 10	238 11
Total lubricants	9, 654	6, 623	2, 512	2, 414	235	249

<sup>1</sup> Subject to revision.

Military necessities have brought radical changes in the manufacture of lubricating oils. The attempt to restrict lubricants used for military purposes to as few grades as possible requires that all those lubricants be of high grade. Not only must they meet the ordinary and heavy-duty needs of tanks, trucks, light automotive equipment, and airplanes, but they must function within the wide range of conditions under which military vehicles operate. Airplane oils must withstand temperatures which, within moments, may change from the warmth of the tropics to the cold of the stratosphere; trucks and tanks serve both in the sand and heat of the desert and in the ice and cold of the Arctic. The two principal qualities needed for such lubricants are high viscosity index and low pour point.

Vital to production of the superoils required for such service is solvent dewaxing, a method developed principally since 1937. Before the use of this process only Pennsylvania-Grade oils could serve for heavy-duty purposes, but by using solvents to dissolve the wax and asphalt, a high-viscosity-index lubricant can be produced from western

and Gulf coast crudes.

But even our best mineral oils are not sufficient in themselves for the severe conditions they sometimes meet. Qualities must be built into them to permit them to lubricate properly at extreme temper-This is done by adding agents-"additives"-that have special qualities, such as oiliness, antioxidation qualities, detergent or cleansing qualities, and fluidity at low temperatures, besides inhibitors to counteract certain detrimental effects of the additives.

Scarcity of chemicals necessitated a restricted use of many additives in oils for nonmilitary vehicles. Chlorine was eliminated wherever possible, and cresol, detergent, and detergent-disperser type additives and extreme-pressure lubricants were designated "not for passenger cars." Use for nonmilitary services of pour-point depressants and oxidation inhibitor-type additives was reduced as much as possible.

Prices of lubricating oils, in general, clung close to their maximums permitted by the Office of Price Administration. Pennsylvania neutrals, however, were an exception. The lowered mileage of passenger automobiles, as well as the slower speeds traveled, has reduced considerably the demand for neutrals from which these lighter oils are made. At the same time, military officials have been demanding all the Pennsylvania-Grade heavy-duty oil that can be made; in consequence, the production of bright stock, from which these heavyduty oils are compounded, has caused accumulation of the neutrals

necessarily produced along with the bright stocks. Stocks of neutrals from Pennsylvania-Grade crude totaled 526,000 barrels on December 31, 1942, compared with 140,000 barrels on the same date in 1941.

Average monthly refinery prices of five selected grades of lubricating oil in the United States, 1941–42, in cents per gallon <sup>1</sup>

	Jan.	Feb.	Mar.	Apr.	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Av- erage for year
1941													
Oklahoma:	100		1		1.11			1					
200 viscosity, No. 3 color, neutral	9. 75	9. 78	9. 75	9. 9	10. 45	11. 21	12. 26	13. 38	14. 56	15. 23	15. 25	15. 25	12. 23
150-160 viscosity at 210°, bright stock, 10-25 pour test	13. 84	14. 2	14. 25	14. 68	15. 83	18. 21	20. 13	21. 08	22, 17	22. 75	22. 75	22. 75	18. 56
Pennsylvania: 200 viscosity, No. 3 color, neu-							1 - 1						
trial, 420–425 flash, 25 pour test	21. 50	21. 50	22. 26	24. 20	27. 95	32.07	35. 52	35, 07	33. 98	33.00	33.00	33.00	29.42
600 steam-refined, cylinder stock, filterable	8.05	8.96	9.40	10.0	11.04	12. 42	13. 60	14. 71	15. 33	16.00	15. 50	15. 50	12. 55
Gulf Coast: 500 viscosity, No. 2½-3½ color, neutral	8. 50	8, 50	8. 50	8.50	8.94	9.00	9. 63	10.00	10.00	10.00	10.00	10.00	9. 30
1942										- 11			Ù is
Oklahoma:		1		1	1	1. 22			1				
200 viscosity, No. 3 color, neutral	15. 25	15. 2	15.00	15.0	15.00	15.00	15. 00	15. 00	15.00	15.00	15.00	15.00	15. 04
150-160 viscosity at 210°, bright stock, 10-25 pour test	22. 75	22. 7	22. 7	22. 7	5 22. 75	22. 75	22. 75	22. 75	22. 75	22. 7	22. 75	22. 75	22. 7
Pennsylvania: 200 viscosity, No. 3 color, neu-													
tral, 420-425 flash, 25 pour test	33. 00	33. 0	33.00	33.0	33.00	33. 00	33. 00	32. 14	30. 67	27. 27	25. 58	24. 59	30. 94
600 steam-refined, cylinder stock, filterable	15. 50	15. 1	15.00	15.0	15.00	15.00	15.00	15.00	15.00	15.00	15.00	15.00	15.06
Gulf Coast: 500 viscosity, No. 2½-3½ color, neutral	10.00	10.0	10.0	10.0	10.00	10.00	10.00	10.00	10.00	10.00	10.00	10.00	10.00

<sup>&</sup>lt;sup>1</sup> National Petroleum News.

The maximum price for the Pennsylvania neutral quoted in the accompanying table was set at 33 cents a gallon on August 4, 1941, by the Office of Price Administration and Civilian Supplies. This constituted a reduction, as the oil had sold as high as 40 cents, and no sales thereafter were for less than the ceiling until the middle of August 1942. After that the price declined throughout the balance of the year, reaching a low of 23 cents in December.

It should be kept in mind that the trend of automobile lubricants has been toward a lighter oil and that with the resumption of peace and normal automobile travel, conditions existing just before the war when neutrals were more popular probably will return. Plans should be made to store excess high-grade neutrals in preparation for that time.

A new Federal excise tax on lubricating oils raised the tax from 4½ cents per gallon to 6 cents, effective November 1, 1942, and the Office of Price Administration provided that the 1½-cent additional tax might be passed to the consumer by adding 1 cent to each sale of 5 quarts or less or the full tax to any sale of more than that quantity.

#### OTHER PRODUCTS

Wax.—Domestic demand for paraffin wax reached a new peak of 546,313,000 pounds in 1942, compared with 523,965,000 in 1941. Exports, however, dropped to 153,410,000 pounds, from 213,075,000

in 1941, making total demand somewhat less than in 1941. dropped to 9,749,000 pounds from 16,542,000, and stocks at the end of the year were 85,400,000 pounds compared with 74,814,000 at the end of 1941.

Production-700,560,000 pounds-was 30,520,000 pounds higher than the 1941 output of 670,040,000 pounds. A gain of 140 percent in the production in Inland Texas was the largest relative increase, but it still left that district with less than 0.5 percent of the total. The only districts where decreases occurred were the East Coast and Louisiana Gulf Coast.

Prices remained throughout the year at the maximum permitted by the Office of Price Administration, effective December 1, 1941. These ranged from 4.25 cents per pound of 122°-124° melting point to 5.50 cents for crude scale wax of 132° and higher and from 5.0 cents for 120°-122° to 10.5 cents for 149°-151° fully refined wax. A change, however, was made in the method of calculating the amount The above prices originally were f. o. b. seller's shipping point, with the freight equalized from certain basing points. An amendment, in force January 30, 1942, made the effective prices those above plus actual shipping costs.

Comparative analyses of statistics for wax in the United States, 1941-42, by months and districts

[Thousands of pounds]

Month and district	Prod	uction		stic de- and	Ex	ports	Sto	ocks
	1941	1942 1	1941	1942 1	1941	1942 1	1941	1942 1
By months:	1							<u> </u>
January February	38, 640	55, 160	30,836	43, 035	13, 229	17 605	120,027	72,800
February	38, 920	52, 920	31, 613	38, 368	10, 174	12 630	119, 150	75,600
March	51, 240	61,600	34, 804	53, 517	13, 766	13 806	121, 887	75,040
April	56 280	52,080	52, 151	45, 349	11,779	12 203	116,096	69,720
May	57, 400	51,800	40, 340	43, 707	14,700		118, 456	69, 160
May June	54,600	57, 960	46, 975	45, 768	15, 605		110, 481	69, 720
Juiv	55 440	50, 680	47, 803	42, 612	16,740		101, 434	68, 040
August September	54, 320	61,040	54,027	44,700	16, 716	7, 380	85, 824	77, 000
September	66, 360	57, 120	53, 828	44, 031	20, 104	12, 249		77, 840
October	67, 760	75, 320	45, 727	55, 494	30, 422	11, 426	75, 467	86, 240
November	68, 880	59, 920	51,086	41, 263	20, 396	18, 377	76, 413	86, 520
December	60, 200	64, 960	34, 775	48, 469	29, 444	17, 611	74, 814	85, 400
Total United States	670, 040	700, 560	523, 965	546, 313	213, 075	153, 410	74, 814	85, 400
By districts:								
East Coast	233, 520	213, 640	h	İ	1	İ	/19, 126	23, 520
		119, 280	11				13, 180	15, 960
Indiana, Illinois, Kentucky, etc. Oklahoma, Kansas, and Mis-	49, 280	57, 960	[]				21, 495	23, 240
Oklahoma, Kansas, and Mis-		,	П	l ·	l	١.	1 21, 100	20, 210
Souri	44 800	57, 960	(2)	(2)	(2)	(2)	4,799	3, 360
Texas Inland Texas Gulf Coast	1,400	3,360	''	''	``	`′	11	280
Texas Gulf Coast	122, 640	140, 560	11	ŀ	Į	i	9, 244	10, 920
Louisiana Gulf Coast Rocky Mountain	89, 320	85, 400	11	]	1	1	3, 427	560
Kocky Mountain	17,080	22, 400	)				3, 543	7, 560
Total United States	670,040	700, 560	523, 965	546, 313	213, 075	153, 410	74, 814	85, 400

Subject to revision.
 Figures not available.

Average monthly refinery price of 122°-124° white crude scale wax at Pennsylvania refineries, 1938-42, in cents per pound <sup>1</sup>

Year	Jan.	Feb.	Mar.	Apr.	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Aver- age for year
1938	2, 52	2. 13	2. 02	1. 93	1. 93	2. 17	2. 29	2, 37	2. 40	2. 39	2, 33	2. 32	2. 23
	2, 39	2. 49	2. 60	2. 73	2. 96	3. 00	2. 95	2, 88	3. 47	4. 95	6, 56	6. 75	3. 64
	6, 21	5. 57	5. 32	4. 79	4. 69	4. 19	2. 93	2, 21	2. 51	2. 81	2, 93	2. 87	3. 92
	2, 73	2. 63	2. 86	3. 28	3. 85	4. 96	5. 13	5, 26	5. 96	6. 25	6, 21	4. 25	4. 45
	4, 25	4. 25	4. 25	4. 25	4. 25	4. 25	4. 25	4, 25	4. 25	4. 25	4, 25	4. 25	4. 25

<sup>&</sup>lt;sup>1</sup> National Petroleum News.

Coke.—Coke output came under close supervision of the Petroleum Administration for War in 1942. The tendency to neglect coke production in favor of fuel oil, when prices for the latter increased, led to a request by the Administrator that certain refineries raise their output. Use of coke was restricted to essential war requirements, principally for the manufacture of electrodes needed for the production of aluminum and other vital commodities.

Comparative analyses of statistics for petroleum coke in the United States, 1941-42, by months and districts

	(thous	iction ands of tons)	Yield (I	ercent)	mand	stic de- (thou- of short ns)	Stocks sands o tor	
	1941	1942 1	1941	1942 1	1941	1942 1	1941	1942 1
By months: January. February. March. April. May. June. July. August September. October. November. December. Total United States.	128. 2 140. 0 144. 4 134. 2 137. 0 157. 8 153. 6 149. 4 150. 8	139. 8 121. 2 108. 4 91. 4 87. 6 101. 0 110. 8 108. 0 123. 0 122. 0 141. 8	0.6 .66 .66 .65 .77 .66 .6	0.6 .54 .44 .55 .55 .55	195. 5 118. 6 114. 5 86. 2 119. 5 116. 0 126. 7 102. 7 102. 7 126. 9 88. 9 285. 8	115.0 97.3 102.9 112.9 74.8 78.7 74.8 76.6 81.7 82.2 57.4 50.1	406. 0 375. 0 375. 0 400. 0 385. 0 382. 0 367. 0 370. 0 362. 0 390. 0 228. 0	245. 8 258. 8 252. 4 201. 0 191. 2 181. 8 175. 0 179. 0 172. 8 183. 6 197. 6 233. 8
By districts: East Coast	4. 4 26. 0 894. 0 181. 4 119. 4 185. 0 49. 4 189. 2	2. 4 25. 2 847. 2 144. 0 75. 0 141. 6 16. 2 37. 6 49. 2	(2) 2 1.8 .7 .9 .3 .7 .4	(3) .2 1.6 .6 .5 .2 .1 .5 .1	(3)	(3)	2.0 9.0 64.0 17.0 51.0 40.0 1.0 35.0 9.0	1.8 2.6 81.6 29.2 48.6 26.6 1.2 20.0 22.2

<sup>1</sup> Subject to revision.

Output of coke in 1942 amounted to 1,338,400 tons compared with 1,648,800 in 1941. Production declined in all districts except Gulf Coast Louisiana, where the output amounted to 16,200 tons—the first material production since 1938. The Indiana, Illinois, Kentucky, etc., district supplied 63 percent of the output.

<sup>2</sup> Less than 0.1 percent.

<sup>3</sup> Figures not available.

Domestic demand, restricted to essential war needs, amounted to 1,004,400 tons compared with 1,628,700 in 1941. Exports were 328,200 tons compared with 279,100 in 1941. The 233,800 tons of toolka were 5,800 above 41

stocks were 5,800 above the record year-end low of 1941.

Asphalt and road oil.—Domestic demand for asphalt was 6,460,200 short tons compared with 6,451,800 in 1941. Production was 6,296,500 tons compared with 6,557,600 in 1941; imports declined from 158,300 tons to 142,500 and exports from 274,100 tons to 171,800. Stocks were 411,000 tons at the end of 1942 compared with 604,000 at the end of 1941.

Domestic demand for road oil declined from 8,980,000 barrels in 1941 to 8,484,000 in 1941. Production dropped from 9,149,000 barrels to 8,039,000 and stocks from 793,000 barrels to 348,000.

Detailed statistics on asphalt and road oil appear in the chapter

on Asphalt and Related Bitumens.

Still gas.—Production of still gas in 1942 totaled 275,054 million cubic feet (equivalent, 76,404,000 barrels) compared with 300,074 million cubic feet in 1941. Of the latter, 283,021 million cubic feet (94 percent) were used as refinery fuel, which, in terms of British thermal units, constituted more than half of all the heat used at refineries.

The Texas Gulf Coast district continued to lead in the production of still gas in 1942, with the Indiana, Illinois, Kentucky, etc., and East Coast districts following in order.

Production of still gas in the United States, 1940-42, by districts

	1	940	1	1941	1942 1	
District	Millions of cubic feet	Equivalent, in thou- sands of barrels	Millions of cubic feet	Equivalent, in thou- sands of barrels	Millions of cubic feet	Equivalent in thou- sands of barrels
East Coast. Appalachian Indiana, Illinois, Kentucky, etc. Oklahoma, Kansas, and Missouri. Texas Inland Texas Gulf Coast. Louisiana Gulf Coast Arkansas and Louisiana Inland Rocky Mountain. California.	38, 804 10, 080 56, 110 22, 698 15, 181 87, 156 9, 616 3, 067 5, 663 25, 045	10, 779 2, 800 15, 586 6, 305 4, 217 24, 210 2, 671 852 1, 573 6, 957	42, 192 10, 065 56, 336 27, 727 16, 913 95, 404 8, 485 4, 406 5, 872 32, 674	11, 720 2, 796 15, 649 7, 702 4, 698 26, 501 2, 357 1, 224 1, 631 9, 076	37, 531 9, 961 56, 398 21, 608 15, 148 85, 337 10, 104 3, 613 5, 556 29, 798	10, 42, 2, 76, 15, 66, 6, 00, 4, 20, 23, 70, 2, 80, 1, 00, 1, 54, 8, 27,
Total United States	273, 420	75, 950	300, 074	83, 354	275, 054	76, 40

<sup>&</sup>lt;sup>1</sup> Subject to revision.

Miscellaneous oils.—Domestic demand for miscellaneous oils amounted to 14,225,000 barrels in 1942 compared with 11,862,000 in 1941.

Production totaled 7,795,000 barrels compared with 6,266,000 in 1941. Of the production in 1941, 4,739,000 barrels were liquefied petroleum gas, and an additional 6,281,000 barrels of this product were transferred from natural gasoline. Detailed analysis of production is not available for 1942, but transfers from natural gasoline in that year amounted to 7,195,000 barrels. Gains in the production of petrolatum, absorption oil, medicinal oil, and specialities in 1941 over 1940 ranged from 7 percent to 40 percent.

Production of miscellaneous oils in the United States, 1940-41, by districts and classes1

#### [Thousands of barrels]

District	Petro- latum	Absorp- tion oil	Medici- nal oil	Special- ties	Lique- fied petro- leum gas	Other	Total
East Coast	94 230 39 35 11 20 1	8 43 51	148	4 43 65	837 - 725 40 29 36 29 23	117 52 43 15 60 171 51 4 51	1, 196 294 850 133 140 283 100 28 178
Total United States	430	130	185	174	1, 719	564	3, 202
East Coast	79 239 47 51	6 10 42 31	211	8 15 46	1, 163 1, 025 71 89	107 31 95 12 26	1, 574 295 1, 213 176 146
Texas Gulf Coast  Louisiana Gulf Coast  Arkansas and Louisiana Inland  Rocky Mountain  California	10 36 —1	14 58	47	57	-17 90 14 24 2, 280	63 32 19 19 47	126 158 33 56 2, 489
Total United States	461	161	258	196	4, 739	451	6, 266

<sup>&</sup>lt;sup>1</sup> Detailed figures for 1942 not yet available.

## WORLD PRODUCTION 2

War damages and dislocation of ocean shipping resulted in a 7-percent decrease in the world production of crude petroleum, if numerous unofficial statistics and estimates can be considered reliable. The outstanding decreases were in Venezuela, the Netherlands East Indies, and the U. S. S. R. The United States, largest producer in the world, showed only a 1-percent decline from 1941 to 1942.

The Western Hemisphere supplied 80 percent of the world output in 1941 and 81 percent in 1942. Lack of shipping caused American and British-Netherlands corporations operating in Venezuela and Colombia to reduce their output. In Peru and Ecuador, however, the foreign companies were able to increase their production. In Argentina the Government enterprise (Y. P. F.) accounted principally for an 8-percent increase from 1941 to 1942.

A decline in exports from 15.8 million barrels in 1941 to 6 3 million barrels in 1942 caused Mexican production to decrease 17 percent, in spite of increased domestic consumption of mineral oils. Export sales were confined to the Western Hemisphere in 1942; and shipping difficulties did not permit the United States and Cuba, the principal purchasers, to take their normal amounts of Mexican oil in 1942.

Canada maintained its 1941 level of production in 1942; and Trinidad apparently increased its output.

By A. H. Redfield, Petroleum Economics Division, Bureau of Mines.

Crude petroleum produced in principal countries of the world, 1938-42, in thousands of barrels

[Compiled by B. B. Waldbauer]

Country	1938	1939	1940 1	1941 1	1942 1
North America:					
Canada				Table 1	
Maria	- 6, 966	7,838	8, 591	10.134	10, 36
Mexico	- 38, 506	42,898	44,036	42, 196 21, 211	35, 15
Trinidad	17,737	19, 270	20, 219	21, 211	
United States	1, 214, 355	1, 264, 962	1, 353, 214	1 400 000	25, 70
United States Other North America	78	112	1, 303, 214	1, 402, 228	1, 385, 479 150
Total North America	1, 277, 642	1, 335, 080	1, 426, 202	1, 475, 919	1, 456, 844
South America:			3		
Argentina	17, 076	18, 613	20,609	01 079	
Bolivia	226			21,873	23, 544
Brazil	- 220	215	288	235	308
Colombia			2	3	31
Colombia		23,857	25, 593	24, 553	10, 593
Ecuador	2, 246	2, 313	2, 349	1. 557	
Peru	15, 839	13, 508	12, 126		2, 278
Venezuela	188, 174			11, 935	13, 629
		206, 470	185, 570	223, 784	147, 740
Total South America	245, 143	264, 976	246, 537	283, 940	198, 123
Europe:					
Albania					100
Albama	752	934	1,497	1, 381	2,002
Czechoslovakia	. 130	120	119	109	100
France	513	500	496	479	
Germany	3, 861				500
Austria	0,001	4, 487	4, 544	4, 438	4, 500
TT	383	693	719	692	900
Hungary	288	1, 103	1,755	2,474	4,000
Italy	101	91	57	77	2,000
Poland	3, 763	3,898			77
Rumania			3, 891	3, 319	3, 400
U. S. S. R. 3		45, 483	42, 182	38, 147	38, 881
U. D. D. R	204, 956	216,866	218,600	238, 150	210,000
Other Europe	9	10	10	10	10
Total Europe 2	263, 243	274, 185	273, 870	289, 276	264, 370
sia:					
Bahrein Island	8, 298	7, 589	7, 074	6 704	. M. COO
Burma	7, 538	7 070		6, 794	7,800
China 4	1,000	7,873	7, 731	7, 762	2, 500
India Daire				10	86
India, British	2,488	2, 327	2, 250	3, 571	2, 500
Iran (Persia)	78, 372	78, 151	66, 221	50, 722	73, 350
Iraq	32, 643	30, 791	24, 225		
	9 511			12,650	14, 700
Netherland sIndies	2, 511	2,654	2, 639	2,659	3,000
Calabatianu Sinules	57, 318	62, 087	62,011	53, 704	9,000
Sakhalin	3 3, 821	3 4, 000	4,000	4,000	4,000
Sarawak and Brunei	6, 913	7,097	7,047		
Saudi Arabia	495			6,864	3,000
277	490	3, 934	5, 365	5, 871	6, 000
Total Asia 5	200, 397	206, 503	188, 563	154, 607	125, 936
frica:					
EgyptOther Africa	1, 581 27	4, 666 27	6, 505 27	8, 546 27	9,000 27
Total Africa	1,608	4, 693	0 500		
ustralia and New Zealand			6, 532	8, 573	9,027
indistributed	4	3	3	3	3
ndistributed	4	4	14	14	15
Grand total	1, 988, 041	2, 085, 444	2, 141, 721	2, 212, 332	2, 054, 318

Approximate production. Data derived in part from World Petroleum, vol. 12, No. 2, February 1941, pp. 20-21, and vol. 13, No. 3, March 1942, p. 88.
 Includes U. S. S. R. fields in Asia, other than Sakhalin.
 Approximate production.
 Unoccupied China.
 Exclusive of U. S. S. R. fields in Asia, other than Sakhalin, which are included with U. S. S. R. in Europe.

Reliable information on petroleum production in Europe is extremely meager. Rumania maintained its level of output from 1941 to 1942. The U. S. S. R. apparently experienced a 12-percent loss owing to military operations on the north side of the Caucasus Mountains. Hungary presumably increased its petroleum production.

Increased military activity in Egypt and Libya and improvement in the supply of tankers enabled Iran, Bahrein Island, and Iraq to enlarge their output of petroleum from 1941 to 1942. On the other hand, deliberate sabotage by retreating Allied armies apparently reduced petroleum production in the Netherlands East Indies, Sarawak and Brunei, and Burma beyond the possibility of full rehabilitation by the invading Japanese.

## FOREIGN TRADE 3

#### IMPORTS

Imports of mineral oils, crude and refined, into continental United States decreased 64 percent from 1941 to 1942. They constituted 2 percent of the total new supply in continental United States in 1942, compared with 6 percent in 1941.

Mineral oils, crude and refined, imported into continental United States, 1941-42, by months 1

			[T	house	nds of	barrel	s]						
Class	Jan.	Feb.	Mar.	Apr.	Мау	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1941													
Crude petroleum Refined products: Gasoline, finished Kerosine	2, 793	3, 371	3, 821 1 43		3, 866	4, 332	5, 331	4, 327 156 81		'		4, 834 67	50, 606 335 191
Distillate fuel oil Residual fuel oil Paraffin wax	421 2, 279 1 2	483 2, 651 7	277 4, 191	195 2, 968 7	300 2, 474		1, 488	463 2, 564 3		2, 469 15	3, 952 12	288 5, <b>54</b> 8 9	5, 074 37, 369 59
Asphalt Unfinished oils, other	275		70 376	258	355				123		124		
19422	5, 771	6, 792	8, 779	7,282	7, 008	7, 427	7, 731	7, 781	10, 093	8, 081	9, 434	10,963	97, 142
Crude petroleum Refined products: Gasoline, finished	3, 554 14				849	540	135	315	236	111	74	248	12, 297 99
Kerosine Distillate fuel oil Residual fuel oil Paraffin wax	13	3, 297 3	19	92 1,483		54 342	521	626		1,838	1, 230	1, 212	17, 645 36
AsphaltUnfinished oils. other	83 63		253 61	1		41	76	61		102 89	-		785 366
	7, 487	7, 077	5, 554	3,003	1, 588	977	772	1, 144	837	2, 561	2, 038	2, 036	35, 074

<sup>&</sup>lt;sup>1</sup> Imports of crude as reported to Bureau of Mines; imports of refined products compiled from data of Department of Commerce; figures may differ slightly from those used throughout other sections of this report.

Subject to revision.

Crude petroleum, residual fuel oil, and distillate fuel oil made up 96 percent of the total imports in 1941 and 95 percent in 1942. Venezuela supplied 74 percent of the crude petroleum imported in 1941 and 55 percent in 1942; Mexico 19 percent in 1941 and 27 percent in 1942; and Colombia 6 percent in 1941 and 18 percent in 1942. Of the residual fuel oil imported in 1941, the Netherlands West Indies furnished 74 percent, Venezuela 22 percent, and Mexico 32 percent. In 1942 the Netherlands West Indies shipped 90 percent

By A. H. Redfield, Petroleum Economics Division, Bureau of Mines.

and Venezuela 5 percent of the imported fuel oil. Of the distillate fuel oil imported the Netherlands West Indies sent 33 percent in 1941 and 53 percent in 1942; Venezuela 24 percent in 1941 and 25 percent in 1942; and Mexico 41 percent in 1941 and 18 percent in 1942.

Receipts of foreign crude petroleum were 76 percent lower in 1942 than in 1941. Imports of residual fuel oil declined 53 percent from

1941 to 1942 and of distillate fuel oil 32 percent.

#### EXPORTS

Continental United States increased its net exports of mineral oils from 11,688,000 barrels in 1941 to 86,055,000 barrels in 1942. This was due principally to a shift from net imports of crude petroleum amounting to 17,368,000 barrels in 1941 to net exports of 21,537,000 barrels in 1942; and to a decrease in net imports of residual fuel oil from 23,255,000 barrels in 1941 to 4,113,000 barrels in 1942. Net exports of motor fuel and of distillate fuel oil were greater in 1942 than in 1941.

In absolute amounts, exports and Territorial shipments of mineral oils, both crude and refined, were 11 percent larger in 1942 than in 1941. The principal gains were in outward shipments of motor fuel and of distillate fuel oil. On the other hand, less kerosine, residual fuel oil, and lubricating oil were exported and shipped to noncontiguous Territories in 1942 than in 1941. Outward shipments of crude petroleum were virtually unchanged from 1941 to 1942.

Mineral oils, crude and refined, shipped from continental United States and including shipments to noncontiguous Territories, 1941-42, by classes and months 1 [Thousands of barrels]

				Trnou	sands of ba	11619]						<del></del>	
Class	January	February	March	April	May	June ·	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total
Crude petroleum	1, 632	1, 256	2, 058	2, 628	4, 428	3, 894	3, 651	3, 275	2, 900	2,840	2, 738	1, 938	33, 238
Refined products:  Motor fuel: <sup>3</sup> Aviation <sup>3</sup> Other	440 1,601	362 891	497 1, 241	63 1, 465	372 1, 216	386 876	239 1, 349	775 1, 925	481 1, 994	1, 143 2, 357	921 2, 229	1, 835 2, 425	7, 514 19, 569
Total motor fuel	1 1 1 1 1 1 1 1	1, 253 82 791 975 744 36 75 74 44	1,738 165 1,028 1,170 703 49 52 105 52	1, 528 180 876 1, 378 775 42 85 128 67	1, 588 171 1, 156 981 961 53 178 142 50	1, 262 112 1, 380 1, 267 831 56 157 103 46	1, 588 110 1, 161 954 754 60 113 103	2, 700 400 2, 300 1, 600 900 60 146 128 59	2, 475 302 1, 283 1, 282 582 72 62 183 41	3,500 828 1,703 1,213 766 108 174 72 56	3, 150 190 1, 445 1, 368 846 73 162 78 46	4, 260 589 2, 207 924 1, 528 105 135 272 115	27, 083 3, 221 16, 925 14, 114 9, 924 761 1, 396 1, 508 660
Total refined	5, 525	4, 074	5, 062	5, 059	5, 280	5, 214	4, 890	8, 293	6, 282	8, 420	7, 358	10, 135	75, 592
Total crude and refined	7, 157	5, 330	7, 120	7, 687	9, 708	9, 108	8, 541	11, 568	9, 182	11, 260	10, 096	12,073	108, 830
1942 4 Crude petroleum	1, 522	1, 336	1, 887	2, 973	3, 709	3, 591	3, 370	4, 073	3, 240	3, 264	2, 826	2, 043	33, 834
Refined products: Motor fuel <sup>2</sup> A viation <sup>3</sup> Other	1, 235 1, 896	664 1, 514	1, 461 1 592	1, 668 1, 098	1, 406 1, 161	2, 594 780	2, 278 1, 148	1, 980 956	1, 113 907	2, 949 1, 009	2, 611 867	2, 716 611	22, 675 13, 539
Total motor fuel. Kerosine. Distillate fuel oil. Residual fuel oil. Lubricating oil. Paraffin wax. Coke. Asphalt. Miscellaneous oils.	1, 080 1, 264 678 63 35 65 53	2 178 247 1,160 786 558 45 55 146 63	3, 053 261 1, 797 917 877 50 59 67	2, 766 368 1, 925 1, 080 657 44 150 95	2, 567 95 1, 151 1, 370 616 31 92 132 43	3,374 212 2,052 1,311 578 42 91 64 51	3, 426 432 4, 180 1, 358 982 35 165 156 46	2, 936 58 1, 569 1, 158 657 26 151 62 63	2, 020 222 1, 705 756 707 44 163 31 54	3, 958 258 2, 572 1, 133 802 41 150 64 48	3, 478 90 1, 516 881 470 66 253 15 49	3, 327 94 2, 009 1, 518 729 63 277 48 75	36, 214 2, 729 22, 716 13, 532 8, 311 550 1, 641 945 657
Total refined	6, 761	5, 238	7, 139	7, 139	6, 097	7,775	10, 780	6, 680	5. 702	9, 026	6, 818	8, 140	87, 295
Total crude and refined	8, 283	6, 574	9, 026	10, 112	9, 806	11, 366	14, 150	10,753	8. 942	12, 290	9,644	10.183	121.129

<sup>&</sup>lt;sup>1</sup> Compiled from the records of the Department of Commerce; figures may differ slightly from those used throughout other sections of this report.

<sup>2</sup> Includes benzol, natural gasoline, and antiknock compounds.

<sup>3</sup> Includes antiknock compounds.

<sup>4</sup> Subject to revision.

### INTERCOASTAL SHIPMENTS 4

Submarine attacks on shipping and diversion of tankers to wartime routes reduced shipments of mineral oils from Gulf coast ports to the East coast by 71 percent. Crude petroleum underwent the greatest decrease 79 percent. Intercoastal shipments of gasoline declined 75 percent; kerosene 65 percent; distillate fuel oil 52 percent; and residual fuel oil 69 percent.

Gasoline was the largest single item in these intercoastal shipments in 1942, constituting 26 percent of the whole. Crude petroleum was 25 percent, residual fuel oil 19 percent, and distillate fuel oil 16

percent.

Mineral oils, crude and refined, shipped from Gulf coast to East coast ports of the United States, 1941-42, by classes

#### [Thousands of barrels]

			01 0011011					
				1942 1				
Class	Jan.	Feb.	Mar.	Apr.	May	June	July	
Crude petroleum	11, 581 7, 848 2, 593 3, 883 5, 218 674 930	6, 179 3, 890 1, 881 3, 212 4, 158 509 680	4, 379 3, 633 1, 476 3, 353 5, 530 430 777	1, 892 3, 779 556 1, 185 2, 064 142 350	1, 242 1, 585 213 1, 037 1, 582 102 230	1, 228 2, 468 305 879 660 130 608	901 1, 890 370 1, 148 1, 035 151 716	
	32, 727	20, 509	19, 578	9, 968	5, 991	6, 269	6, 211	
			194	į <u>2</u> 1		- 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1	1941 2	
Class	Aug.	Sept.	Oct.	Nov.	Dec.	Total	(total)	
Crude petroleum	1, 166 1, 676 92 1, 042 502 6 697	729 1, 197 285 1, 490 234 14 559	679 1, 200 254 794 532 1 96	1, 376 354 1, 049 878	580 1,881 491 1,283 987	30, 998 32, 423 8, 870 20, 346 23, 380 2, 159 5, 717	147, 288 130, 534 25, 300 42, 620 75, 923 8, 148 956	
	5, 181	4, 508	3, 556	4, 138	5, 257	123, 893	430, 769	

Office of the Petroleum Coordinator and the Petroleum Administration for War.
 Petroleum Conservation Division, U. S. Department of the Interior.

By A. H. Redfield, Petroleum Economics Division, Bureau of Mines.

## NATURAL GAS

By G. R. HOPKINS AND H. BACKUS

### SUMMARY OUTLINE

	Page		Page
Summary	1127	Consumption—Continued.	1. V
Salient Statistics	1128	Field	1153
Legislative and legal review	1129	Carbon -black manufacture	1153
Gross production	1130	Petroleum refineries	1153
Marketed production	1132	Electric public-utility power plants	1153
Wells	1133	Portland-cement plants	1153
Technologic developments	1134	Other industrial	1153
Review of field developments, by States	1134	Mixed gas	1156
Consumption	1149	Interstate shipments	1156
Treated for natural gasoline	1151		1160
Domostic and commercial	1151		

#### SUMMARY

The natural-gas industry attained new peaks in 1942 as it responded to heavy demands from war industries and to expanding civilian requirements. Final figures for the year are not yet available, hence

the following summary is largely estimated.

Marketed production of natural gas in 1942 totaled 3,055 billion cubic feet—9 percent above the peak of 2,813 billion reported in 1941 (see fig. 1). All the major classes of consumption increased except field use, which declined 1 percent, and gas used in carbon-black manufacture, which fell 8 percent. Increased field use for gas-lift operations in a few States did not quite counterbalance a recession in drilling operations in the country as a whole, and the slump in the rubber industry which furnishes the principal market for carbon black slowed production of that commodity. The largest percentage increase over 1941 was in fuel used at petroleum refineries, which was 25 percent above the 1941 figure; substitution of natural gas for fuel in place of fuel oil and possibly still gas is the probable cause of this Gas used at portland-cement plants gained 19 percent and gas used for miscellaneous industrial purposes 15 percent. classes contributed heavily to war requirements. Natural gas is especially adapted for furnishing controlled heat for the manufacture of precision parts for guns, planes, tanks, and ships. An estimated 25 percent of total deliveries is reported to have been used by war industries in 1942.

Salient statistics of natural gas in the United States, 1938-42

	1938	1939	1940	1941	1942 1
Marketed production:					
California million of cubic feet_	315, 168	348, 361	351, 950	374, 905	414.00
Louisiana do do	283, 899	294, 370	343, 191	403, 855	
Oklahoma do	263, 164	250, 875	257, 626	234, 054	459,00
Texas	000 472	979, 427	1,063,538	204, 004	277,00
West Virginia do	134, 342	159, 226	1,000,000	1, 086, 312	1, 156, 00
Other Statesdo	416, 516	444, 497	188, 751 455, 166	207, 681 505, 851	220, 00 529, 00
Total productiondo				- 000,001	020,00
Total production	_ 2, 295, 562	2, 476, 756	2,660,222	2, 812, 658	3, 055, 000
EXPORES.	1				
To Canadado	- 94	76	90	121	130
To Mexicodo	1,743	3,046	5, 473	7, 345	8, 670
To Mexico do Imports from Canada do	372	. 131			
Consumption:					
Domestic do	367,772	391, 153	443, 646	442, 067	501 000
Commercial do	114. 296	118, 334	134, 644	144, 844	501,000
Industrial:	111, 200	110,004	101, 044	144,044	170,000
Industrial: Fielddo	659, 203	680, 884	711, 861	686, 158	600 000
Carbon-black plants do	204 050	347, 270	368, 802	365, 377	680, 000
Petroleum refineries do	109, 741	97, 685			335, 533
Electric public-utility power plants 2		91,000	128, 007	148, 127	185, 000
million of cubic feet_	169, 988	191, 131	183, 156	205, 156	234, 113
Portland-cement plants 3do	37, 336	40, 233	41, 949	54, 208	64, 540
Portland-cement plants 3 do Other industrial do	510, 811	607, 075	642, 594	759, 255	876, 014
Total consumptiondo Domesticpercent of total	2, 294, 097	2 473 765	2, 654, 659	2, 805, 192	2 040 000
Domestic percent of total	16	16	2,004,009	16	3, 046, 200
Commercial	1 E		5		16
Industrialdo	79	79	78	5	_6
		19	10	79	78
Domestic thousands	8,570	8,888	0.045	0 =00	
Commercial do	1 '00"		9, 245	9,730	10,010
Industrial 4	39	715	741	767	810
Industrial 4 do Number of producing gas wells	39	40	41	43	45
		53, 530	53, 880	54,880	55, 500
Total thousands of dollars Average per M cubic feet cents	113, 571	120, 243	120, 493	138, 508	156,000
Average per M cubic feetcents_	4.9	4.9	4.5	4.9	5.1
Value (at points of consumption) of gas consumed:					
Domestic thousands of dollars	273, 070	. 287, 600	315, 515	318, 093	250 000
Commercial do	56, 247	58, 494	64, 399		356,000
Industrial	177 000			68, 398	79,000
	111,200	187,627	197, 090	233, 547	275, 338
Total valuedodoAverage per M cubic feet:		533, 721	577, 004	620, 038	710, 338
Domestic cents Commercial do	74.2	73.5	71.1	72.0	71.1
Commercialdo	49.2	49. 4	47.8	47.2	46. 5
		9.6	9.5	10.5	11.6
Domestic and commercial do Domestic, commercial, and industrial	68.3	67. 9	65. 7	65. 9	64.8
conte	21.8	21.6	21.7	22. 1	23.3
reated for natural gasoline:					
Quantitymillions of cubic feet		2, 150, 000	2, 471, 400	2, 763, 300	3,000,000
Ratio to total consumption	89	87	93	2,100,000	98
		-		- "	- 00

1 Subject to revision.
2 Federal Power Commission.
3 Chapters on Cement in Minerals Yearbook.
4 Exclusive of oil- and gas-field operators.

The average value of natural gas at the wells in 1942 was 5.1 cents a thousand cubic feet, compared with 4.9 cents in 1941. production in the eastern fields where higher prices prevail and a strengthening of the price in Texas, which produced over a third of the

total output in the United States, contributed to the 0.2-cent gain. The average value at points of consumption was 23.3 cents in 1942 compared with 22.1 cents in 1941. A gain of 1.1 cents in the average price of industrial gas and an increase in the relative proportion of the higher-priced domestic-commercial gas outweighed declines in the average prices of domestic and commercial gas. total value of natural gas consumed in the United States in 1942 was \$710,338,000—15 percent over the peak of \$620,038,000 reported in 1941.

Gas treated for natural gasoline approximated 3,000 billion cubic feet in 1942, compared with 2,763 billion in 1941. The proportion of total consumption was 98 percent in 1942 and 99 percent in 1941.

Exports to Mexico were 8,670 million cubic feet in 1942—18 percent over the 1941 figure. Mixed gas exported to Canada contained




FIGURE 1.-Production and value of natural gas in the United States, 1916-42.

130 million cubic feet of natural gas compared with 121 million in

Consumers using natural gas in the United States in 1942 totaled 10,865,000—3 percent more than in 1941.

### LEGISLATIVE AND LEGAL REVIEW

Conservation continued to be a paramount consideration in 1942, not only as regards the long-term program of producing more efficiently and with less waste, but the conservation of manpower and equipment as well.

The Federal Power Commission was given a wider scope of authority early in the year, and a number of orders were issued regulating the activities of gas companies. Existing pipe-line companies were ordered to file applications with the Commission by May 8, 1942, to obtain certificates of necessity to remain in business and were required to obtain authority before building new lines or changing old ones. general, the policy was to cut down competition between companies and to avoid extending lines into territory already supplied with gas

or to districts where other fuels are readily available.

The Office of Petroleum Administration for War issued a number of orders with regard to drilling. Order M-68 permitting only one well drilled to each 640 acres was modified on February 12 to allow more drilling in New York, Pennsylvania, West Virginia, Ohio, and Kentucky. This order was revised further on June 20 to permit drilling gas wells on 40-acre tracts in Missouri and parts of Oklahoma and Texas. Drilling in the Hugoton field in Kansas and Oklahoma was suspended by Order M-68-6 issued on September 3. than 20 wells in the field were reported to have no pipe-line connections, and it was decided that no more drilling was necessary until the available production was utilized.

In September the War Production Board ordered that the line of the Panhandle Eastern Pipe Line Co. be connected to that of the Ohio Fuel Gas Co. in Ohio, to assure a supply of Texas gas to supplement that from the eastern fields, preventing a possible shortage in the area supplied by the latter company. Effective November 30, deliveries to nonresidential consumers were suspended unless such distribution was specifically authorized by the Board. Such restrictions had already been in effect in a few States, but the new ruling applied to all States. Sales of heating equipment to residential consumers were curtailed and prohibited in places where delivery of the gas to residential, commercial, or industrial consumers had not been authorized. When shortages were imminent, gas companies were also required to curtail deliveries to domestic consumers. December 12, gas deliveries were ordered suspended in some parts of Kansas, Oklahoma, and Missouri to plants which were equipped with stand-by facilities for using coal, and to all refineries with any type of alternative fuel facilities. Early in January 1943 the War Production Board was empowered to cut off either manufactured- or natural-gas consumers that could convert to other fuels without undue expense or inconvenience.

The Office of Price Administration placed a price ceiling on both wet and dry natural gas, effective October 7, 1942, except for rates charged by public utilities or others specifically excluded from the order. The price could be retroactive to May 11.

### GROSS PRODUCTION

In the absence of final figures on marketed output, gross production of natural gas in 1942 has not been estimated. The 1941 figure is estimated at 4,103,500 million cubic feet or 11 percent more than the 1940 total. Production from gas wells increased 9 percent to 2,279,590 million cubic feet and from oil wells 14 percent to 1,823,910 million. There were sharp decreases in New York and Mississippi, where gas fields are becoming depleted and oil fields are small. Most of the other States made gains in output from both gas and oil wells. Decreased production from oil wells was noted in Illinois, Michigan, Oklahoma, Pennsylvania, and West Virginia.

Repressuring operations are gaining rapidly in importance; 644,379 million cubic feet of gas were returned to formations in 1941 compared with 362,916 million in 1940. Notable gains were made in Louisiana and Texas, where the cycle process is being extensively used in condensate fields; for example, repressuring in Texas rose from 294,000 million cubic feet in 1940 to 527,159 million in 1941 and in Louisiana from 21,000 million to 56,008 million. Repressuring was reported in Michigan for the first time in 1941. Arkansas, Kansas, and Oklahoma were the only States that reported declines from the 1940 volumes.

1

Gross production and disposition of natural gas in the United States, 1940-41, by States, in millions of cubic feet

	Estin	nated produc	tion 1	E	stimated o	lisposition	
State	From gas wells	From oil wells	Total	Marketed production	Repres- suring	Stored in ground	Losses and waste
1940							
rkansas alifornia	8, 500 25, 200	32, 500	41, 000 430, 000	14, 379 351, 950	860		25, 76
olorado	25, 200	404, 800 400	2,900	2, 533	12, 145	6, 287	59, 613 36
linois	1,100	129, 900	131, 000	8, 359	749		121, 89
linoisdiana	1, 200	2,000	3, 200	1, 137			2, 06
ansas	75,000	40,000	115,000	90, 003	2,817	3 1, 162	21, 91
entucky	54,000	5,000	59,000	53, 056	210	4 483	4, 71
nniciono	285 000	150,000	435, 000	343, 191	21,000		70, 80
ichigan	10,000	4,000	14,000	12, 648		ll	1, 35
ichigan ississippi issouri ontana	6, 500	300	6,800	6, 365			43
Issouri	390	10	400	310			9
ontana	25, 900	1,300	27, 200	26, 231			969
ew Mexico	32,000	94,000	126, 000	63, 990	31	l	61, 97
ew York hio	15, 100	100	15, 200	12, 187	12	8 414	2, 69 5, 21
Lio	46, 400	3, 600	50,000	40, 639	3, 050	6 3, 706	5, 21
klahoma ennsylvania exas	90, 000 96, 000	220, 000 6, 000	310, 000 102, 000	257, 626 90, 725	14, 463 826	794 71,723	36, 74
THIS YIVAHIA	1, 100, 000	475, 000	1, 575, 000	1, 063, 538	294, 000	1, (23	9, 21 216, 93
est Virginia	193,000		205, 000	188, 751	3, 583	8 426	9, 57
yoming	22,000	12,000 18,000	40,000	27, 346	9, 170	420	3, 48
ther States	5, 390	10,000	5, 400	5, 258	8, 170		14
	2, 095, 180	1, 598, 920	3, 694, 100	2, 660, 222	362, 916	14, 995	655, 96
1941 10							
rkansas	10, 200	34, 800	45, 000	19, 148	781		25, 07
alifornial	36, 500	423, 500	460,000	374, 905	21,000	6,000	58, 09
olorado	3, 100	200	3, 300	3, 256			4
inois	900	101, 500	102, 400	10,053	1,958	539	89, 85
diana	1,400	2, 100	3, 500	1, 522			1, 97
ansas	77, 000	46,000	123,000	111, 121	2, 345	597	8, 93
entucky	71,000	5, 200	76, 200	69, 067	480	11 440	5, 37
ouisiana	375, 100	199, 700	574, 800	403, 855	56, 008	72	114, 93
ichigan	11,900	3, 200 590	15, 100	13, 916	741	/2	37 77
ississippiissouri	4, 450 200	10	5, 040 210	4, 268 196			"1
ontono	27,000	1, 500	28, 500	28, 499			1
ontana ew Mexico	34, 100	98, 600	132, 700	64, 655	557		67, 48
ew Mexico	12, 400	100	12, 500	10, 456	14	13 340	1, 69
hio	47, 500	3,700	51, 200	41, 858	3, 213	13 3, 166	5, 16
klahoma	99, 100	176, 300	275, 400	234, 054	11, 420	1,677	28, 24
nnsylvania	99, 300	5,700	105,000	92, 819	921	14 2, 841	9,96
Xas	1, 126, 000	691,000	1, 817, 000	1, 086, 312	527, 159		203, 52
est Virginia	212, 100	11, 200	223, 300	207, 681	4,772	18 579	7, 35
voming	24, 600	19, 000	43, 600	29, 284	13, 010		1, 30
yomingher States •	5, 740	10,000	5, 750	5, 733			1,00
	2, 279, 590	1, 823, 910	4, 103, 500	2, 812, 658	644, 379	16, 251	630, 21

<sup>1</sup> Marketed production plus quantities used in repressuring, stored in ground, lost and wasted (see foot-

<sup>1</sup> Includes gas (mostly residue gas) blown to the air and transportation losses but does not include direct waste on producing properties, except where data are available.

3 Produced approximately as follows: 373 million cubic feet in Oklahoma, 525 million in Texas, and 264 million in Kansas.

 <sup>4</sup> Produced approximately as follows: 183 million cubic feet in West Virginia and 300 million in Kentucky.
 5 Produced approximately as follows: 109 million cubic feet in Pennsylvania and 305 million in New York.
 6 Produced approximately as follows: 397 million cubic feet in Kentucky, 2,216 million in West Virginia, and 1,093 million in Ohio.

 <sup>7</sup> Produced approximately as follows: 178 million cubic feet in Kentucky, 424 million in West Virginia, and 1,121 million in Pennsylvania.
 8 Produced approximately as follows: 148 million cubic feet in Kentucky, 7 million in Pennsylvania, and 271 million in West Virginia.
 North Dakota, South Dakota, Tennessee, Utah, Virginia, and Washington.

<sup>16</sup> Subject to revision. 11 Produced approximately as follows: 267 million cubic feet in Kentucky, and 173 million in West Virginia

ginia.

13 Produced approximately as follows: 334 million cubic feet in New York, and 6 million in Pennsylvania.

14 Produced approximately as follows: 1,865 million cubic feet in West Virginia, 962 million in Ohio, 320 million in Kentucky, and 19 million in Pennsylvania.

14 Produced approximately as follows: 1,251 million cubic feet in Pennsylvania, 1,110 million in West Wirginia, and 480 million in Kentucky.

15 Produced approximately as follows: 341 million cubic feet in West Virginia, 215 million in Kentucky, and 23 million in Pennsylvania.

Gas storage in depleted fields has been successful in a number of States, and that method of building up a reserve to be drawn upon in times of peak demand is gaining importance. In 1941, 16,251 million cubic feet of natural gas were reported stored in 10 States compared with 14,995 million stored in 8 States in 1940 and 8,032 million stored in 6 States in 1939.

Reported losses and waste of natural gas totaled 630,212 million cubic feet in 1941—a 4-percent decline from 1940 and 7 percent below 1939. This record is creditable but leaves room for improvement, even though much of the total waste is unavoidable.

## MARKETED PRODUCTION

The marketed production of natural gas in 1941 was 2,812,658 million cubic feet—a 6-percent gain over the 1940 record of 2,660,222 million cubic feet. Decreases were reported in Mississippi, Missouri, New York, and Oklahoma. All other States important in gas output made increases. The major producing States having the largest were: Kansas, 23 percent; Louisiana, 18; West Virginia, 10; California, 7; and Texas, 2. Texas retained first place in amount produced, and Louisiana displaced California in second place.

West Virginia produced 57 percent, Louisiana 45 percent, and Texas 19 percent over State requirements; the surplus was piped to

other States and some Texas gas went to Mexico.

The value of natural gas at the wells turned upward in 1941 after dropping steadily for many years. The average was 4.9 cents a thousand cubic feet compared with 4.5 cents in 1940. The average value at points of consumption was 22.1 cents in 1941 compared with 21.7 cents in 1940.

Natural gas produced in the United States and delivered to consumers, 1937-41, by States, in millions of cubic feet

Year	Arkan- sas	Cali- fornia	Colo- rado	Illi- nois	Indi- ana	Kan- sas		en- cky		nisi- na	Mic igai		Aissi sippi		New Mexi- co
1937 1938 1939 1940	11, 301 10, 107 14, 379	329, 769 315, 168 348, 361 351, 950 374, 905	3, 186 1, 904 2, 015 2, 533 3, 256	1, 040 1, 169 2, 746 8, 359 10, 053	1, 551 1, 299 791 1, 137 1, 522	80, 55	3 46 6 47 3 53	, 719 , 163 , 771 , 056 , 067	283, 294, 343,	899 370 191	9, 0 10, 1 10, 7 12, 6 13, 9	65 26 48	13, 34 13, 65 14, 52 6, 36 4, 26	66 21, 21 27 23, 17 35 26, 23	6 50, 706 8 60, 284 1 63, 990
Year	New York	Ohio	Okla- homa	Penn- syl- vania	Texa	as   N	est ir- nia	w <sub>3</sub>		Oth Stat		Tot			Average per M cubic feet (cents)
1937 1938 1939 1940 1941	21, 325 39, 402 29, 222 12, 187 10, 456	35, 257 36, 469 40, 639	296, 260 263, 164 250, 875 257, 626 234, 054	76, 54 93, 88 90, 72	7 882,		, 342 , 226 , 751	26, 26, 27,	023 678 614 346 284	5, 8 5, 6 5, 5	980 2, 350 2, 369 2, 568 2, 929 2,	295, 476, 660,	562 756 222	528, 354 500, 698 534, 240 577, 939 621, 333	

Natural gas produced and consumed in the United States in 1941, by States

	Produced	d and de	delivered to liveries in o	Consumed, including receipts from other States						
_	Quantity	y	Estimated at we		Value at po		Quantit	y	Value at pe	
State	M cubic feet	Per- cent of total	Total	Average per M cubic feet (cents)	Total	Average per M cubic feet (cents)	M cubic feet	Per- cent of total	Total	Average per M cubic feet (cents)
Ala							32, 023, 000		\$7,359,000	23.0
Ariz							18, 213, 000	.6	5, 711, 000	31.4
Ark	19, 148, 000	0.7	\$764,000	4.0			46, 933, 000	1.7	7, 793, 000	16.6
Calif	374, 905, 000					25.8	374, 905, 000	13. 4 . 9	96, 673, 000	25. 8 33. 8
C010	3, 256, 000	.1	121,000	3.7	714, 000	21.9	26, 574, 000 5, 124, 000	.2	8, 983, 000 3, 552, 000	69.3
D. C							2, 378, 000	.1	599,000	25. 2
Ga							23, 975, 000	.8	8, 713, 000	36. 3
ni	10, 053, 000	.4	186,000	1.9	1,668,000	16.6	98, 634, 000	3.5		43.8
Ind	1, 522, 000				906, 000			1.1	11, 614, 500	38.7
Iowa							24, 589, 000	.9	8, 826, 000	35.9
Kans	111, 121, 000	3.9	4, 512, 000	4.1	36, 552, 000	32.9	109, 059, 000	3.9	22, 550, 000	20.7
Ку			9, 041, 000		28, 769, 000	41.7	20, 170, 000		8, 708, 000	43. 2
La	403, 855, 000	14.4	13, 085, 000	3.2	71, 089, 000	17.6	222, 025, 000	7.9	25, 190, 000	11.3
Md					0.700.000	62. 7	6, 587, 000 37, 290, 000	1.3	2, 436, 000 29, 484, 000	37.0 79.1
Mich	13, 916, 000	.5	1, 787, 000	12.8	8, 722, 000	02. 7	22, 672, 000	1.3	9, 291, 000	
Minn Miss	4, 268, 000	.1	170,000	4.0	1, 084, 000	25. 4	20, 813, 000	.7	5, 642, 000	27.1
Mo	196,000		16, 400		100,000	51.0	58, 138, 000	2.1	22, 044, 000	37. 9
Mont	28, 499, 000	1.0	1, 305, 000		7, 597, 000	26.7	24, 751, 000	.9	6,078,000	24.6
Nebr	20, 100, 000		.,, 000, 000				19, 205, 000	.7	7, 109, 000	37.0
N. Mex	2 64, 655, 000	2.3	1,067,000	1.7	11, 339, 000	17.5	39, 138, 000	1.4	4,674,000	11.9
N. Y	8 10, 456, 000			19.6	7, 853, 000	75.1	25, <b>3</b> 84, 000	.9	19, 588, 000	77. 2
N. Dak	47,000		1,000		16,000	34.0	1,741,000	.1	676, 000	38.8
Ohio	41, 858, 000	1.5	6, 835, 000	16.3	21, 232, 000	50.7 12.7	136, 251, 000 209, 395, 000	4.9 7.5	69, 179, 000 21, 340, 500	50.8 10.2
Okla	234, 054, 000			2.8	29, 821, 000	46.3		5.0		
Pa S. Dak	4 92, 819, 000 7, 000	3.3	19, 910, 000 400	21. 5 5. 7	42, 974, 000 2, 000	28.6	6, 580, 000	3.0	2, 226, 000	33.8
Tenn	10,000		1,000	10.0	5,000	50.0	22, 495, 000	.8	6, 379, 000	28.4
Tex	\$1,086,312,000	38.6	22, 269, 000		162, 344, 000	14.9	875, 620, 000	31.2	68, 101, 000	7.8
Utah	5, 562, 000	. 2	191,000			20.6	16, 667, 000	. 6	3, 458, 000	
Va	106,000	(1) (1)	1,100	10.4	94,000	88.7	1, 166, 000	(1)	1,068,000	
Wash	1,000	(1)	100		2,000	200.0		[ (j) ~	2,000	200.0
W. Va Wyo		7.4	25, 171, 000 902, 000		81, 957, 000 5, 687, 000	39. 5 19. 4		3.2	21, 782, 000 3, 143, 000	24. 6 16. 9
Total:	2, 812, 658, 000	100.0	120 500 000	4.0	621, 333, 000	99 1	2, 805, 192, 000	100.0	620, 038, 000	22. 1
1941	2, 812, 658, 000	100.0	100, 000, 000		577, 939, 000	01.1	2,000, 102, 000	1200.0	577, 004, 000	21.7

### WELLS

Producing gas wells, as of December 31, 1941, numbered 55,500-3 percent more than the 53,880 reported at the end of 1940. A 2,911 wells were drilled during the year, it would appear that 1,291 were abandoned. Actually abandonments probably were fewer, for some of the productive wells reported are old ones that have been reconditioned or deepened.

During 1942 2,597 wells were drilled—11 percent less than the number of completions in 1941. An increased demand for production usually results in greater drilling activity; but difficulty in obtaining materials, Government restrictions, and shortages of manpower re-

tarded operations during the year.

Less than 0.05 percent.
 Includes 1,154,600 M cubic feet piped to Mexico.
 Includes 27,000 M cubic feet piped to Canada.
 Includes 94,000 M cubic feet piped to Canada.
 Includes 6,191,000 M cubic feet piped to Mexico.

## Gas wells in the United States, 1940-42, by States

State	Producing Dec. 31, 1940	Drilled during 1941 <sup>1</sup>	Producing Dec. 31, 1941	Drilled during 1942 i
Arkansas California Colorado Illinois Indiana Kansas Kentucky Louisiana Michigan Mississippi Missouri Montana New Mexico New York Ohio Oklahoma Pennsylvania Tennessee Texas West Virginia Wyoming Other States 3	2, 030	20 23 4 13 56 102 255 111 97 4 18 59 19 18 701 159 386	200 1110 20 950 2,090 22,570 1,640 450 1130 450 1110 2,030 6,700 2,400 18,300 (2) (3) (3) (4) (3) (3) (3) (3) (3) (3) (3) (3) (3) (3	77 25 1 1 14 21 88 210 88 74 1 7 69 15 26 471 102 595 536 6 3
얼마 보인 중요하는 경기의 공연기	53, 880	2, 911	55, 500	2, 597

From Oil and Gas Journal and State sources.
 Tennessee included with Kentucky.
 North Dakota, South Dakota, Utah, and Virginia.

### TECHNOLOGIC DEVELOPMENTS

When the shortage of materials became serious because of the war, renewed efforts were made to find substitutes and additional sources of various commodities. New experiments were made with natural gas and methods found by which its various hydrocarbons could be separated.

The components of natural gas have been found to be valuable in the manufacture of a wide range of war products, from nylon, ammonia, and synthetic rubber to an anaesthetic that is being used increasingly because of its harmless effects.

The necessity for conserving cargo space has brought dehydrated foods to the fore. Natural gas has been found an ideal source of heat to be used in drying fruits, vegetables, and even shrimp. Several California firms are producing dehydrated foods by the ton, and the industry is becoming important in the State. Some food experts believe that the general public will use dehydrated products increasingly in the near future.

# REVIEW OF FIELD DEVELOPMENTS, BY STATES

Arkansas.—Joe W. Kimzey, State geologist, has submitted information taken from the records of the Arkansas State Department of Revenues regarding developments in Arkansas.

All the gas-well drilling reported was in the northwest gas fields. One well was drilled in Crawford County to a depth of 5,104 feet, two in Franklin County to 5,755 and 2,900 feet, respectively, and one in Logan County to 2,690 feet. All were dry holes and abandoned. Pope County a well was drilled to a total depth of 2,830 feet in sec. 22, T. 10 N., R. 21 W. Gas was found in the second sand with an initial production of 17,263,000 cubic feet and in the third sand with initial production of 9,562,000 cubic feet.

Arkansas produced 29,560 million cubic feet of gas during 1942—a 20-percent increase over the 24,617 million cubic feet reported in 1941. The dry-gas fields in the northwestern area produced 5,367 million cubic feet—16 percent less than the 1941 output. In the southern area production increased 33 percent over the 1941 total to 24,193 million cubic feet. Union County ranked first in output with 10,085 million cubic feet, Columbia was second with 9,080 million, and Miller third with 4,440 million. Johnson, with 2,439 million, was the only county in the northwest field that produced over a million cubic feet of gas.

California.—Demands for low-gravity oils to meet war requirements centered activity in California during 1942 in the relatively shallow heavy-oil zones in the South Joaquin Valley area. Such drilling contributed virtually nothing to natural-gas reserves. Information on gas developments in the State during the year is taken from a report from E. F. McNaughton, California Railroad Commission.

Steady drilling in the proved area of the Wilmington field of the Los Angeles Basin resulted incidentally in the formation of secondary gas caps and a correspondingly higher gas: oil ratio in the field as a

whole, so that more gas was available.

The Bowerbank gas field was discovered in the South Joaquin Valley area when an existing well was redrilled. Other wells drilled in the vicinity were failures. The Roberts Island dry-gas field, which apparently was not very large, was the only important discovery during the year. The proved area of the Riverdale gas field was extended 2½ miles northeast, resulting in increased activity in that area. The northern boundary of the Raisin City gas field was determined by an

unsuccessful completion.

One of the main gas lines from the San Joaquin Valley to the San Francisco area was converted into an oil line in May 1942. To replace this, a 22-inch line was built to connect the metropolitan area with the Rio Vista gas field. The new line, with rearranged facilities of other lines, made available 140 to 150 million cubic feet of gas over the 180 million formerly transported daily by the converted line. Sharp gains in consumption, caused by war production and additional requirements by civilian and military users, made this additional supply necessary. Only about 100 million cubic feet were brought daily from the oil fields, which formerly furnished most of the total supply. Another line was built to connect the Rio Vista field with other areas formerly served with casinghead gas.

Dry gas from the Buttonwillow and Trico fields was run through a line that formerly carried casinghead gas. Because dry gas has a lower heating value than casinghead gas, the California Railroad Commission established an automatic heating-value clause to adjust consumer rates according to the quality of gas served. This provision is in general effect, except for interruntible surplus service.

sion is in general effect, except for interruptible surplus service.

The nearly depleted Playa del Rey field was tested for underground storage in 1942, and at the end of the year construction was progressing on permanent compressor facilities. It is estimated that 3 billion cubic feet of gas can be stored in the field. Between 15 and 20 million cubic feet probably will be withdrawn daily. The field lies near the heart of the Los Angeles area where peak demand occurs and will furnish an easily accessible auxiliary supply.

Another supply of gas will be stored in a water-seal gas holder with a capacity of 10 million cubic feet, which was completed and placed

in service late in 1942 in Los Angeles.

The commission made a survey during the year to determine the daily peak demand for and availability of gas to assure war industries and essential civilian services an uninterrupted supply. It was concluded that demands, though greatly augmented, could be met with existing facilities. Available reserves, as of July 1, 1942, were estimated at 11,007 billion cubic feet and unavailable reserves at 1,456 It was thought that the daily peak demand would total 1,635 million cubic feet. Production for the first half of the year was 206,645 million cubic feet, of which 203,410 were utilized and 3,235 blown to Comparable figures for 1941 were 191,858, 184,554, and 7.304 million, respectively. Figures for the latter half of the year are not available. Dry-gas production in 1942 was 104,867 million cubic feet compared with 36,450 in 1941. The sharp gain was due principally to pipe-line connections with gas fields to replace casinghead gas. Another factor was Government restrictions on production in fields having high gas: oil ratios, so that withdrawals could not be varied to meet fluctuating demands, which forced distributors to depend on dry-gas supplies.

Gas sales totaled 264,444 million cubic feet in 1942 compared with

232,751 in 1941—a 14-percent gain.

Colorado.—Little drilling was done in Colorado during 1942. One well was completed in the Powder Wash field with an initial production of 11,660,000 cubic feet, and the field was extended ½ mile northeast. One well was deepened and the deepening of another started. An exploratory well at Douglas Creek found less than 1,000,000 cubic feet of gas in the basal Dakota sand at 4,433–35 feet. Drilling was continued to the Weber quartzite in search for oil, but work was suspended for the winter at a depth of 7,313 feet. Information regarding developments in Colorado was supplied by L. G. Snow, acting supervisor, Geological Survey, United States Department of the Interior, Casper, Wyo.

Hiawatha field, with a 37-percent increase, and Powder Wash field, with a 136-percent increase, supplied 76 percent of the total output of the State. All of the fields increased production except Berthoud and Garcia. Gross output, by fields, in millions of cubic feet, follows: Hiawatha, 2,727.1; Powder Wash, 1,125.6; Wilson Creek, 303.0; Thornburg, 167.5; Berthoud, 42.4; Garcia, 16.5; and

Craig, 4.9.

Marketed production in 1942 totaled 4,029.5 million cubic feet—a gain of about 49 percent over the 2,713.0 million marketed in 1941. Gross production was 4,387.0 million cubic feet—52 percent over the 1941 figure and twice the amount reported in 1940. It is estimated that 53.8 million cubic feet were used in the field and 303.7 million lost. Of the latter amount, 291.2 million were in the Wilson Creek field, which does not yet market gas.

Illinois.—A. H. Bell, geologist, and C. W. Carter, assistant geologist, Illinois Geological Survey, have reported natural-gas developments

in Illinois during 1942.

The Russellville gas field had 5 gas completions within proved territory in 1942, making a total of 53 in the district. The average initial production of the new wells was approximately 2 million cubic

A CONTRACT OF THE PROPERTY OF

feet daily. Three of the new wells produced from the Bridgeport and two from the Buchanan sand. At the end of the year the field had 270 acres proved in the Bridgeport sand and 1,600 in the Buchanan. Marketed production from the district was 1,472 million cubic feet compared with 863 million in 1941.

The Ayers field, covering 335 acres, had one gas completion in 1942, making a total of eight wells in the area. Gas comes from the Bethel sandstone at a depth of about 950 feet. Production was virtually the

same as in 1941.

Daily average production of casinghead gas from the Louden oil field in 1942 was estimated at 8.4 billion cubic feet, with an average daily output at the end of the year approximating 20 million cubic feet. Comparable figures for 1941 were 13.7 billion and 36 million. The greater portion of the gas was treated for natural gasoline, and 6 million cubic feet of the residue gas were injected into the producing sands daily. A pipe-line company was furnished with residue gas to supply St. Elmo, Brownstown, and Vandalia. The same company also received 50 thousand cubic feet daily from a well in the field that produced from the basal Pennsylvanian sandstone.

Gas produced from the Salem oil field was estimated at 23.7 billion cubic feet in 1942, with an average daily output of 63 million cubic feet compared with 35.4 billion and 82 million, in 1941. Four gasoline plants processed an average of 49.8 million cubic feet a day. One company returned approximately 5 million cubic feet of residue gas daily to the producing sand, and another supplied residue gas to Salem, Centralia, and Mount Vernon; the quantity approximated

800,000 cubic feet daily at the end of the year.

A small amount of residue gas from a gasoline plant near Hoodville in Hamilton County, that began operation in December, was injected into the producing sands through several input wells, marking the beginning of a large-scale pressure-maintenance system in that area. The New Harmony Consolidated oil field had an estimated produc-

The New Harmony Consolidated oil field had an estimated production of 8.7 billion cubic feet of casinghead gas in 1942, with daily production approximating 21 million cubic feet at the end of the year. About 1.5 million cubic feet of residue gas from a plant that began operations in the field in July were returned to the producing sands daily during the latter half of the year.

The Albion pool, Edwards County, supplied brick plants at Albion with an estimated 100 million cubic feet of gas until the end of the first quarter of 1942, when the plants closed. The field produced

approximately 2 million cubic feet of gas daily.

It is estimated that 84.4 billion cubic feet of gas were produced from oil fields discovered after January 1, 1937, but a large part was burned in flares.

Marketed output of natural gas in Illinois in 1942, exclusive of field uses, totaled 2,573.4 million cubic feet, a 51-percent gain over the

1,699.4 million cubic feet produced in 1941.

Indiana.—Ralph E. Esarey, State geologist, and Dr. George V. Cohee, assistant State geologist, report that no large gas reserves were discovered in Indiana during 1942. Only 21 gas wells were drilled during the year—35 less than in 1941 and all in previously discovered fields. Their total initial production was 11,148,500 cubic feet.

Total marketed production of all fields during 1942 was 1,627.3 million cubic feet, 20 percent over the 1,355 million reported in 1941.

This gain was due largely to a 29-percent increase in the Rockport field, which supplied approximately 37 percent of the total output, and to increased production from the Unionville field. Production from the major fields, in millions of cubic feet, was as follows: Rockport, 594.3; Unionville, 239.9; Greensburg, 210.8; Glendale-Hudsonville, 157.0; North Glendale, 102.4; and Laconio (Harrison), 100.0.

Gas from the Griffin oil field, Posey and Gibson Counties, is being used for repressuring the field, after being treated for natural gasoline at a plant that began operations in August 1942 on the Illinois side of the Wabash River. By March 1943 over 1.5 million cubic feet were being injected into the producing sands daily through 14 input wells. Gas from the same plant is also being used to repressure the Waltersburg sand in the Ribeyre Island portion of the New Harmony field through four input wells.

Kansas.—The State had 88 gas-well completions in 1942 compared with 102 in 1941. Information on gas developments was supplied

by Charles P. Kaiser, geologist, Kansas Geological Survey.

The Hugoton field was an outstanding exception to the sharp decline in drilling in most of the major fields in the western part of the State. There were 21 completions in Hugoton in 1942 compared with 11 in 1941. The new wells had a daily potential of 324.4 million cubic feet, and production in the field increased from 36.4 billion cubic feet in 1941 to 41.4 billion in 1942. Much of the drilling was in Grant County near the carbon-black plant at Ryus. In all, 299,919 million cubic feet had been drawn from the Hugoton field by the end of 1942.

McLouth, in Jefferson and Leavenworth Counties, eastern Kansas, was the field of greatest activity in 1942. There were 44 gas-well completions compared with 39 in 1941. A total of 89 gas wells has been drilled in the field since production was begun in 1941. The output was 4,438.9 million cubic feet in 1942 compared with 1,667 million in 1941.

Completions in the Cunningham-Cairo field in Kingman and Pratt Counties dropped from 16 in 1941 (with a total daily potential of 190.5 million cubic feet) to 4 in 1942 (with a total daily potential of

41.4 million).

Other completions in the western area were two in the Peace Creek oil pool in western Reno County and two in the Medicine

Lodge pool.

Thirteen wells were drilled in eastern Kansas. Completions were made in Allen, Chautauqua, Douglas, Elk, Franklin, Greenwood, Johnson, and Nasaka Canata.

Johnson, and Neosho Counties.

Two discovery wells were completed in western Kansas—one in the Deerhead pool, Barber County, and one in the Belpre pool, Edwards County. The first had an initial potential of 4 million cubic feet from the Viola limestone, the second 25 million from the

Lansing-Kansas City group of sands.

Production by the major fields, in billions of cubic feet, was: Hugoton, 41.4; Otis, 11.0; Medicine Lodge, 9.9; McLouth, 4.4; Burrton, 3.9; Thurber, 3.3; and Lyons, 0.6. The output of most of the large fields increased, whereas that in some of the smaller ones declined. Western Kansas supplied the major part of a total daily potential of 615.5 million cubic feet. The total for 1941 was 825.4 million cubic feet.

The state of A state of the sta

It is estimated that marketed production in Kansas in 1942 was

103 billion cubic feet compared with 99 billion in 1941.

Kentucky.—During 1942 210 gas wells were drilled in Kentucky, or about 10 percent below the high mark of 1941, according to information supplied by Mrs. Louise B. Freeman, assistant State geologist, Kentucky Department of Mines and Minerals. Completions in the four most active counties were: Pike, 74; Floyd, 51; Knott, 37; and Martin, 25. Of the total output, 65 percent in Pike, 66 in Floyd, 79 in Knott, and 53 in Martin County came from the Devonian-Mississippian black shales.

Clay and Jackson Counties were next in rank, with 8 wells each. In Jackson County 24 wells with an average rock pressure of 140 pounds have been drilled since development started there in 1934. The gas is found at 1,100 to 1,200 feet depth and comes from the Niagara dolomite (Coniferous) sand; output has been greatly increased since it has been found that the wells respond to acidizing. The field has become important, even though the gas is not being marketed.

Five wells were drilled during the year in the Johnson County field, 4 miles west of Paintsville; Knox and Magoffin Counties each

had one well.

There was little gas development in western Kentucky during 1942. Louisiana.—Drilling in Louisiana resulted in 88 gas completions in 1942—a 21-percent decline from 1941. Northern Louisiana had 50 completions, with 373,160 acres proved for gas; Southern Louisiana had 38 completions, with 40,885 proved acres.

Only one-fourth of the 48 wildcat wells drilled in the Gulf Coast area were successful, and of the 12 only 2 were completed as gas wells.

Distillate fields led in importance in the area.

A well blew out in Arcadia Parish in October 1942 and was still out of control at the end of the year in spite of all efforts to check it. In December it was flowing 523 barrels of oil and distillate and 49,-220,000 cubic feet of gas at a depth of 10,447 feet. A relief well was being drilled and was down to 10,025 feet as the year ended.

One of the most important discoveries of 1942 was a well 3 miles southwest of Krotz Springs in the Branch area of St. Landry Parish, which opened a new distillate pool in December. At 11,398 feet it was the deepest wildcat drilled in that area but was plugged back to 9.327 feet.

Distillate was found in the extreme southern part of Bayou Sale field in St. Mary Parish; it comes from a new sand located at 10,703

feet. The well was drilled to a depth of 12,000 feet.

Development in Northern Louisiana shifted in 1942 from the Wilcox sand, which predominated in 1941, to the deeper Pettit and Smack-over limes. The Monroe field was the most active in the State, with 30 completions, followed by the North Lisbon in Claiborne Parish and the Nebo-Hemphill field in LaSalle, with 4 completions each. The following data were furnished by H. W. Bell, Division of Min-

The following data were furnished by H. W. Bell, Division of Minerals, Louisiana Department of Conservation. The total natural-gas production in Louisiana in 1942 was 669,136 million cubic feet, of which 463,695 million (69 percent) were from gas wells and 205,441 million (31 percent) from oil wells. Northern Louisiana produced 388,274 million cubic feet of dry gas and 46,131 million of casinghead gas. Southern Louisiana produced 75,421 million cubic feet of dry gas and 159,310 million of casinghead gas. The Monroe field re-

mained the major gas-producing area in Louisiana, with an output of 217,915 million cubic feet, or 47 percent of the total dry-gas production. The field comprises 61 percent of the gas acreage of the State. Parishes having largest output were: Union, 100,084 million cubic feet; Morehouse, 68,425; Webster, 55,890; Ouachita, 49,439; Caddo, 29,912; and Bossier, 28,501. There are 36 parishes in the State having dry-gas production from about 70 gas fields.

Michigan.—The following information on natural-gas developments in Michigan in 1942 was furnished by F. R. Frye, petroleum engineer,

Michigan Department of Conservation.

In all, 74 gas wells were completed in 1942 compared with 97 in 1941. Previously discovered gas fields in Clare and Osceola Counties were the main points of interest during the year. Of the 74 wells drilled, 30 were in the Marion field, where about 9,500 acres are proved, and 11 in the Evart field, extending the proved acreage there to about

2,100 acres.

Four wells were drilled in the Riverside pool in Missaukee County, the proved acreage approximating 2,240 acres. Two discovery wells were completed, but no additional drilling was done in their vicinity up to the close of the year. The Don Rayburn-Mee No. 1 well in sec. 4, T. 19 N., R. 3 E., was drilled in Arenac County in search for oil. It was put down to the Dundee sand, which was dry, then plugged back to the Berea sand, where it was finished as a gas well, having 300,000 cubic feet initial production and a pressure of 830 pounds. The new pool was tentatively called the North Adams. In December, the Belvidere Oil Co. completed its State No. 1 well for gas at a depth of 1,489 feet in the Michigan Stray sand in Fork Township, Mecosta County. The initial open flow was 1,010,000 cubic feet and the well-head pressure over 500 pounds a square inch.

A desulfurization plant was built in the Riverside pool and put in operation in December 1942, to bring the sulfur content of the gas within the requirements of the Public Service Commission. This field is the first where it has been found necessary to process gas from

the Michigan Stray sand.

A main gas-transmission line, started in 1941 from the Ohio State line to Saginaw and Kalamazoo, was completed in 1942. A request for permission to build a line from the Austin gas pool, which is being used for storage, to the Six Lakes pool was denied by the War Production Board.

Reported production of natural gas reached an all-time high of 17,749 million cubic feet—approximately 17 percent over the 1941

figure of 15,092 million.

Mississippi.—H. M. Morse, supervisor of the Mississippi State Oil and Gas Board, reports that the Jackson field continued to be the main source of natural gas in Mississippi in 1942. The field had 23 gas wells producing during the year. One new well was completed in 1942; none was abandoned.

Production in the field has declined steadily since 1939, when the peak of 15,233 million cubic feet was attained. The output in 1942 was 2,084 million—85 percent less than the peak year and 46 percent

less than the 1941 figure.

Large quantities of gas are used for pumping in the Tinsley, Vaughan-Pickens, and Pickens-Sharpsburg oil fields, and a smaller amount was burned in flares.

THE PARTY OF THE P

The gas: oil ratio is so low in the Cary oil field that the gas is

not used.

Missouri.—Gas completions in Missouri dropped from 18 in 1941 Wells drilled in 1942 were as follows: Bates County, 2, to 7 in 1942. initial open flow 550,000 cubic feet; Caldwell County, 1, initial open flow 200,000 cubic feet; and Platte County, 4, initial open flow 400,000 cubic feet.

As yet no arrangements have been made to utilize the gas from the

Polo field in Caldwell County, discovered in 1940.

The above information was supplied by Frank C. Greene, geologist,

Missouri Geological Survey.

Montana.—Wells drilled in Montana totaled 69 in 1942 compared with 59 in 1941. Data on natural-gas developments were taken from a report by L. G. Snow, acting supervisor, Geological Survey, United States Department of the Interior, Casper, Wyo.

Bowdoin and Cedar Creek fields reported 56 of the gas completions, but all had small initial production. The other 13 were in the Cut Bank, Kevin-Sunburst, and Hardin fields. Total daily initial pro-The other 13 were in the Cut duction of the new wells was 87,265,000 cubic feet. The old fields in Montana need continual drilling to compensate for declines in pressure Some of the old wells were cleaned, repaired, or deepened and volume. to augment production. Two minor discoveries were made, one on the Fred and George Creek nose in T. 37 N., R. 2 E., and one at Conrad Butte in T. 29. N., R. 1 W., but they will not be used unless considerable quantities of gas are developed.

Bowes, Dry Creek, and Kevin-Sunburst were the only fields that did not have increased production in 1942. The Cut Bank field, which produced 45 percent of the total output, made a 21-percent gain over 1941, and Cedar Creek, next in rank, gained 4 percent. The following table shows production in Montana, by fields.

Natural gas produced in Montana in 1942, by fields, in thousands of cubic feet

Field	Marketed gas pro- duction	Gas used for repres- suring	Estimated field use	Estimated waste
Bowdoin Bowes Box Elder Cedar Creek Cut Bank Devon Dry Creek Hardin Haystack Butte Kevin-Sunburst Whitlash	3, 137, 543 477, 361 484, 147 6, 890, 539 13, 554, 518 1, 017, 969 89, 518 91, 636 2, 731, 448 1, 046, 139	22, 820	600,000	3, 000 500 500 8, 000 50, 000 1, 000 600 15, 000 78, 670

Gross production in the State in 1942 was 31,012 million cubic feet-13 percent over the 27,483 million produced in 1941 and 21 percent over the 1940 total. Marketed production totaled 29,910 million cubic feet—an increase of 2,591 million (9 percent) over that of The Kevin-Sunburst field was the only area in which repressuring was reported, 23 million cubic feet being used for that purpose in 1942 compared with 7 million in 1941. Field use consumed 1,000 million compared with 21 million the previous year, and losses were cut from 137 million in 1941 to 79 million in 1942. The amount of gas treated for natural gasoline exceeded the 1941 figure by 12 percent. A plant at Cut Bank treated 11,891 million cubic feet to produce 2,684,000 gallons of natural gasoline, 201,000 of propane, and 1,548,000 of butane, and in the Dry Creek field another plant processed 128 million cubic feet to produce 70,000 gallons of natural gasoline.

The Cut Bank and Kevin-Sunburst areas were connected by a

25-mile line built during the year.

New Mexico.—Of the 12 gas wells drilled in New Mexico in 1942, 8 were in the southeastern and 4 in the northwestern part of the State. This compares with 13 in the southeastern and 6 in the northwestern areas in 1941. The new wells had total initial productions of 107,010,000 cubic feet and 35,720,000 cubic feet, respectively. Three San Juan County wells found gas in the Dakota sand on the Barker Creek structure.

According to information supplied by Foster Morrell, acting supervisor, Geological Survey, United States Department of the Interior, Roswell, N. Mex., natural-gasoline plants treated 103,704 million cubic feet of natural gas in 1942—a decrease of over 5 percent from the 1941 throughput. Domestic, commercial, and industrial consumers in Lea County used over 42 percent (44,132 million cubic feet) of the gas after it was treated for natural gasoline. In Eddy County 75 million cubic feet of residue gas were marketed. The total of these two amounts represents a 21-percent gain over the 36,472 million marketed in 1941. Gas used for gas lift and field consumption and vented without treatment for natural gasoline amounted to 47,299 million cubic feet in 1942—approximately 2½ times the 19,289 million similarly accounted for in 1941. Total production in the southeastern area probably increased more than 20 percent over the 1941 output.

In the northwestern area, 4,022 million cubic feet of gas were used by domestic, commercial, and industrial consumers, leaving 125 million for fuel and wastage. Production increased 13 percent over

the 1941 figure.

New York.—The total output of wells drilled in New York in 1942 continued the decline that began 5 years ago. C. A. Hartnagel, State geologist, reports that unless new reserves are found the total production of the State will drop to the comparatively low level maintained before gas was discovered in the Oriskany sand. Known reserves are being rapidly depleted, and efforts to find new ones have

met little success.

Out of 26 wells (most of them exploratory) drilled to the Oriskany sand in 1942, only 6 were productive, compared with 18 out of 42 in 1941. Tompkins County was the most active district in 1942, but efforts to develop the pool resulted in only 2 small producers. Steuben County had only 4 successful completions in 1942, compared with 14 in 1941. Allegany County had 13 gas completions in 1940, 2 in 1941, and none in 1942. Five dry holes drilled in Allegany County in 1942 were over 4,700 feet deep and in Steuben County 4 were over 5,000 feet. New wells were located as follows: Tompkins County, 11; Steuben County, 9; Allegany County, 6.

No important developments occurred in any of the proved Oriskany pools, and the discovery of new supplies of gas appears discouraging. Only two or three wells were added in the small Trenton limestone field in Oswego and Oneida Counties, and the output continued to be negligible. A few wells were added to the large number of producers in the old Medina fields of western New York.

North Dakota.—According to Wilson M. Laird, State geologist, no new natural-gas developments took place in North Dakota during 1942. The only well drilled was in Oliver County in search for oil,

and it was dry.

The pipe line that supplies gas in eastern Montana and a number of communities in the Dakotas took 121,955,000 cubic feet of gas from eight wells in the Cedar Creek field in the southwestern part of the State. Apparently the gas was used as an auxiliary supply, for none was taken between May and September, when demand for domestic fuel is comparatively light.

Ohio.—The following data were taken from reports by Kenneth

Cottingham, chief geologist, Ohio Fuel Gas Co.

Under adverse conditions resulting from the war, the total number of gas wells drilled in Ohio in 1942 was 33 percent less than the record of 1941 and below the number of completions in any year since 1938. The daily average initial production of the new wells was 5 percent less than that of wells drilled in 1941. It is estimated that one-tenth of the State acreage was under lease to oil and gas operators at the beginning of 1942, but many of the leases were said to have been

surrendered toward the end of the year.

The Clinton sand remains the chief source of gas in the State, although completions in that formation were 16 percent and the average open-flow capacity 17 percent less than in 1941. No significant new areas were discovered, and no important additions were made to the proved acreage. Little drilling was exploratory. A well drilled in Bearfield Township, Perry County, gave every indication that a small Clinton pool had been discovered. It had an initial daily open flow of 1,390,000 cubic feet, but two wells drilled nearby were dry. In Plain Township, Wayne County, a small pool was opened, and about 500 acres were proved. A discovery well having an initial volume of 4,500,000 cubic feet was completed near the end of the year in the southwestern part of Wellington Township, Lorain County, at a depth of about 2,400 feet. The pool is thought to comprise about 350 acres.

Little was done toward finding new production in the Oriskany sand, though it is thought to have possibilities. One well completed in Liberty Township and four in Wheeling Township, Guernsey County, north of the old Cambridge field, averaged 3,300 feet in depth and 1,456,000 cubic feet initial daily open flow. About 1,500 acres were proved in the Oriskany sand, but it is thought that the field will be small. In Mayfield Township, Cuyahoga County, four wells with an average initial open flow of about 2,327,000 cubic feet were drilled to a depth of 1,890 feet. In Richfield Township, Summit County, a well was developed with an initial volume of 238,000 cubic feet. Two attempts to find gas in the Oriskany sand in Meigsville Township, Morgan County, and in Adams Township, Washington County, resulted in dry holes.

No unusually deep drilling was done during 1942. The deepest gas well was in Fairfield Township, Tuscarawas County; production in this well was found in the Clinton sand at 5,313 feet. The initial

volume was 898,000 cubic feet. Another deep test, probably to the Trenton sand, drilling at 6,850 feet found the Clinton sand 18 feet

thick at a depth of 5,398 feet, but it was dry.

The productive sands, number of wells drilled, and average initial production per well, in thousands of cubic feet, were as follows: Clinton, 273 wells with 904 thousand cubic feet average initial volume; Shallow, 90 with 351; Berea, 86 with 168; Oriskany, 10 with 1,682; Ohio shale, 7 with 131; and Newburg, 5 with 783.

A well in York Township, Morgan County, proved to be the most

A well in York Township, Morgan County, proved to be the most productive of the year. It was 4,261 feet deep and had an initial daily open flow of 11,700,000 cubic feet and an initial rock pressure of

1.030 pounds.

Gas wells were drilled in 30 counties in 1942 compared with 35 in 1941. Morgan County, not included in the 10 most active counties in 1941, ranked first in number of gas completion in 1942; Meigs held second place, with 21 fewer wells drilled; Medina, eighth in rank in 1941, was third, with 10 more wells drilled; Licking, first in 1941, dropped to fourth place, with 78 fewer completions. Counties of greatest activity and number of wells drilled in 1942 were: Morgan, 43; Meigs, 42; Medina, 33; Muskingum, 33; Licking, 24; Washington, 24; Tuscarawas, 23; and Wayne, 23.

Oklahoma.—Gas completions in Oklahoma dropped 42 percent

Oklahoma.—Gas completions in Oklahoma dropped 42 percent or from about 175 in 1941 to 102 in 1942. Much of the drilling was in old areas of proved production. No notable new fields were discovered. Wildcatting increased 26 percent, but very little new production was found. The wildcat wells completed for gas were located as follows: Hughes County, 2; Pittsburg, 2; and Comanche, LeFlore, McIntosh, Okfuskee, Pottawatomie, Sequoyah, and Texas, 1 each.

Activity in the Hugoton gas field was stopped during the year by order of the Petroleum Administration for War. The Oklahoma part of the field, which covers most of Texas County, is the largest known gas reserve in the State. It is estimated to have a 33-year supply of gas, as measured by the present rate of total production of all fields. The field is as yet virtually untouched, only about 0.3 percent of the

estimated original reserve having been produced.

According to information supplied by Dan O. Howard, petroleum engineer, Oklahoma Corporation Commission, natural-gas output gained 6 percent in 1942 compared with 1941. Total production amounted to 276,532 million cubic feet. Oil wells produced 151,064 million (55 percent) and gas wells 125,468 million (45 percent). The daily average production approximated 758 million cubic feet. Ninety-five percent of the homes in the State are built to use only natural gas as fuel, and each household averages 95,000 cubic feet of gas a year.

Exports of natural gas to the north and east of Oklahoma continued the increase that began in 1938, largely because of increased industrial demand. A total of 50 billion cubic feet—30.6 percent of the total amount available in the State for domestic and industrial

consumption—was transported to other States during 1942.

Carbon-black plants in Oklahoma utilized approximately 10 billion cubic feet of gas during 1942. One chemical plant is proving that natural gas has growing importance in the manufacture of such byproducts as formaldehyde, methanol, and related chemicals obtained by direct oxidation of the gas.

The commission is intensifying its efforts to prevent waste of gas in the oil fields and to regulate production in the gas fields to insure

maximum recovery.

Pennsylvania.—Information regarding natural-gas developments in Pennsylvania was supplied by J. G. Montgomery, vice president, United Natural Gas Co. The shallow gas fields were the focal point of gas developments in 1942, as was true in 1941. Some drilling is still being done in the deep fields; but production continues to decline, and the fields appear to be almost exhausted. During the year 738

shallow wells were drilled; 80 percent produced gas.

New developments in the southwestern part of the State have proved approximately 2,200 acres in the Armbrust pool, Hempfield Township, Westmoreland County. Total initial volume of the 75 productive wells in the pool was about 48 million cubic feet a day. Nine wells in the Big Injun sand of western Fayette and eastern Greene Counties had average initial capacities of over 1 million Greene Counties had average initial capacities of over 1 million cubic feet a day, and 16 wells in Greene, Allegheny, Indiana, Washington, Armstrong, and Westmoreland Counties approximated the same amount. Jefferson County (with 135 wells drilled), Clarion (with 91), Elk (with 63), and McKean (with 49), were the most active of the central Pennsylvania counties in 1942. Others having developments were Clearfield, Forest, Mercer, Venango, and Warren, where a total of 46 wells was drilled. Highland and Ridgway Townships, Elk County, Jenks Township, Forest County, Oliver and Polk Townships, Jefferson County, and Bell Township, Clearfield County, each had a well with an initial open-flow capacity of over 1 million each had a well with an initial open-flow capacity of over 1 million cubic feet.

Very little new production was found in the deep fields. Fayette County field, four wells were completed in the Summit gas pool; their initial open flow capacity was 141,000 cubic feet, 11,875,000 cubic feet, 11,700,000 cubic feet, and 1,500,000 cubic feet. Gas was found in the fractured Onondaga chert and the underlying Oriskany The complex faulting of this field makes drilling difficult. In Potter County a well in Bingham Township having an initial open-flow capacity of 185,000 cubic feet a day and one in Wharton Township having a capacity of 600,000 cubic feet a day were completed. The first well in Pennsylvania to produce gas in commercial quantities from the Newburg member of the Lockport dolomite was drilled in Worth Township, Mercer County. It had an initial capacity of 159,000 cubic feet a day.

Unsuccessful deep tests included two each in Potter, Tioga, and Lawrence Counties and one each in Greene, Beaver, and Westermoreland Counties. In Tioga County the Salina series below the Oriskany and Helderberg sands, in Lawrence and Mercer Counties the Lockport dolomite, in Westmoreland County the Helderberg below the Oriskany sand, and in Erie County the Trenton limestone were all found to be unproductive.

The area where no Oriskany sand was encountered was extended

further by the two wells drilled in Mercer County.

Much more natural gas was produced in Pennsylvania during 1942 than in previous years. The increase is entirely in the shallow fields, as production from the deep fields continued to decline. The output from the deep fields has dropped steadily, as the following figures show: 2,500 million cubic feet in 1942, 3,750 million in 1941, 6,500 million in 1940, and 30,000 million in 1939—a 92-percent decline between 1939 and 1942. Figures of production from the shallow fields are not available.

South Dakota.—The status of natural gas in South Dakota remained unchanged in 1942, according to E. F. Rothrock, State geologist. Gas from a few artesian wells at Pierre and Fort Pierre and on a few ranches near the Missouri River continued to be used.

A drilling program on large acreages that have been under lease for over a year is promised in the spring of 1943, but there was no activity

during 1942.

Tennessee.—According to Kendall E. Born, associate geologist, Tennessee Department of Conservation, production of natural gas in Tennessee comes from the Sunbright oil field in Morgan County and the Jamestown gas field in Fentress County. Gas is found in the Mississippian limestone in the former and the Trenton limestone in the latter county; both formations are fissured and fractured.

No production figures are available for the Sunbright field for 1942; in the Jamestown field 7,378,000 cubic feet of gas were marketed from

six wells.

Texas.—In all, 238 gas wells were drilled in Texas in 1942 compared

with 294 in 1941—a decline of 19 percent.

The Texas Panhandle and Texas Gulf districts are the only two areas in which the reported number of gas completions gained over those in 1941. Completions in the Panhandle increased 18 percent, or from 49 in 1941 to 58 in 1942. Known gas areas in the Panhandle were enlarged by completions in Hansford and Sherman Counties. The Texas Gulf district had 38 completions in 1942-2 more than were reported for the previous year.

Less than half as many gas wells were drilled in 1942 as in 1941 in the North Central and Southwest districts and less than one-third as many in East Texas. West Texas had only three less in 1942 than

in 1941.

Wildcatting was active in North Central Texas, but only 1 of the 105 exploratory wells drilled in the district was reported as a gas well. A discovery well was drilled in the Gulf Coast region in Matagorda County north of the Bay City field and 3 were drilled in West Texas. A new gas field was opened in Victoria County in Southwest Texas on November 1 by a well that had an initial production of 162 million cubic feet. One successful wildcat well was drilled in Jim Wells County and one in Dimmitt County. The new Sarco gas field in Goliad County, Southwest Texas, was opened by a well 9 miles southeast of Goliad. The well had an open flow of 180 million cubic feet of gas and 50 barrels of distillate. As the year closed, a wildcat well was making distillate and gas at a depth of 8,542 feet, on a drill-stem test in Starr County, 11/2 miles from production. It is one of the deepest active operations in the Rio Grande Valley.

Data on natural-gas operations have been supplied by Jack K. Baumel, Railroad Commission of Texas. The total production of natural gas in 1942 was 1,917 billion cubic feet—an increase of 5.5 percent over the 1,817 billion produced in 1941. Gas lines already in operation were adequate for transmitting gas to meet sharply increased demands, so that there was no problem of transportation, such as confronted the petroleum industry. Deliveries to pipe lines increased from 65.973 million cubic feet in January 1942 to 71.768

million in December.

Of the total output, 1,271 billion cubic feet (66 percent) were sweet gas, 238 billion (13 percent) sour gas, and 408 billion (21 percent) casinghead gas. These figures indicate a 13-percent increase over 1941 in the production of sweet gas, whereas sour gas decreased 7

and casinghead gas 6 percent.

Cycling- and repressuring-plant operations increased 2 percentfrom 570 billion cubic feet in 1941 to 580 billion in 1942. This was an 82-percent gain over the 1940 figure. Gas processed for natural gasoline totaled 904 billion cubic feet, a 4-percent decline from the 945 billion treated in 1941. Carbon-black plants used 295 billion cubic feet of gas in 1942, 10 percent less than the 329 billion used in Gas vented to the air decreased 19 percent in 1942 compared with 1941.

Utah.—Gross production of natural gas in Utah was 4,390 million cubic feet in 1942-7 percent less than the 4,724 million reported in 1941 and only 1 percent over the output in 1940. Only 6 million cubic feet of the total output in 1942 were not marketed, 1 million being used in the field and 5 million lost. There were 20 million not marketed in 1941 and 45 million in 1940, according to figures furnished by L. G. Snow, acting supervisor, Geological Survey, United States Department of the Interior, Casper, Wyo.

A plant near Farnham utilized 149 million cubic feet of carbon dioxide from the Farnham dome in the manufacture of dry ice. com-

pared with 102 million in 1941.

No drilling was done in the State during the year.

Virginia.—A report from William M. McGill, assistant State geologist, Virginia Conservation Commission, gives information regarding natural-gas developments in Virginia. Gas in commercial quantities was discovered in the State in a well completed in June 1931. Five other wells, four of which produced gas, were drilled between that time and February 1940. Gas from the wells was turned into a 4-inch line in March 1938 to supply Bristol, Va., and Bristol, Tenn. A well was completed in 1941 in the Lower Mississippian limestone of Washington County at a depth of 3,910 feet. Another in the northwestern part of Rockingham County was shut down after gas was found at 2,992 feet in the Devonian sand.

A small gas well was completed in January 1942 on the Early Grove anticline in Scott County. It found gas in the Little Valley limestone (Lower Mississippian) at a depth of 3,670 feet. The initial daily production was 139,000 cubic feet and the initial pressure 1,300 pounds. It was stated later that it would yield 125,000 cubic feet daily and that the pressure had built up. A second well is reported to have been drilled in the Ewing district, Lee County. Drilling was stopped when gas was found at 1,100 feet. It is thought that oil might be found if the well were deepened to 1,400 feet.

Washington.—The Northwestern Natural Gas Co., which formerly distributed natural gas to towns in the Yakima Valley region, has reported that the gas wells in the Rattlesnake Hills field (from which its supply was obtained) were completely depleted in 1941, and the company has changed to butane-air gas for distribution to its customers.

West Virginia.—Information on natural-gas developments in West Virginia has been supplied by David B. Reger, consulting geologist.

Morgantown, W. Va.

Various wildcats extended the proved area of existing gas pools in West Virginia in 1942 but opened no strictly new ones. Out of 53 wildcats drilled, 27 were completed as gas wells and 6 as oil wells. About 51,000 additional acres were proved for gas in old fields, and the opening of new pools by wells previously drilled was confirmed. It is probable that the new proved gas reserves represent a substantial increase over withdrawals.

The State had 536 gas completions during 1942, with a total daily open flow of 1,228,501,000 cubic feet compared with 558 wells reported drilled in 1941 with a total daily open flow of 949 million cubic feet. These figures indicate a 4-percent decline in number of wells drilled in 1942 but a 29-percent increase in total daily capacity. During the year, 76 old wells were deepened, adding 26,034,000 cubic feet to production, compared with 86 wells and 56 million cubic feet in 1941.

Drilling increased in the deep Oriskany sand in 1942, and 205 out of 242 tests were successful. This compares with 166 commercial completions in 1941. The Oriskany sand furnished 86 percent of the initial production during the year compared with 75 percent in 1941. Most of the Oriskany gas comes from the Charleston field in Jackson, Kanawha, and Putnam Counties. Only 2 of the 15 tests drilled in other areas found Oriskany gas in commercial quantities, and they were small. The Charleston field is well defined to the north and east by a number of dry holes. It might be extended to the south as far as northern Boone County, where 6 small Oriskany Ten or twelve wells showing tight or thinnedwells have been drilled. out sands indicate a limit to its extent to the west. It is estimated that nearly one-half of the available gas has been recovered from the proved area. About 120 billion cubic feet were withdrawn in 1942.

The Trace Fork field in Putnam County was the most active of the shallow fields, with 40 completions in the Big Lime, Berea, and Brown Shale sands. The Spurlockville field in Lincoln County and the Villa Nova in Braxton and Clay Counties were next in rank, with

17 completions each.

The counties of greatest activity and the number of gas completions in each were: Jackson, 150; Kanawha, 59; Putnam, 48; Upshur, 33;

Boone, 30; Calhoun, 29; Clay, 28; Gilmer, 26; and Ritchie, 18.

Production was raised in Kanawha and Raleigh Counties and other areas by acidizing lime wells. The practice of storing gas in depleted sands to build up a reserve to meet peak demands is gaining in im-One company reported six such projects in use in Pennsylvania and West Virginia in 1942 and two others under test.

Marketed production in West Virginia is estimated at 220 million cubic feet in 1942—a 6-percent gain over the 208 million reported

in 1941.

Wyoming.—Three gas wells were drilled in old fields in Wyoming during 1942, one each in the Big Sand Draw, North Baxter Basin, and Pilot Butte fields. The total daily initial flow was 38 million cubic feet, compared with 56 million from five wells drilled in the old fields in 1941. The Pilot Butte field has no pipe-line connections, and the gas is used for field operations only.

Three gas wells, with a total initial flow of 14 million cubic feet, were drilled in the new Sherard field. The field was connected with the gas system from the Lost Soldier area to Sinclair, Wyo., by 9 miles

of welded line.

L. G. Snow, assistant supervisor, Geological Survey, United States Department of the Interior, Casper, Wyo., reports production from 43 fields in Wyoming in 1942. Big Medicine Bow continued the decline that began several years ago. Salt Creek had 583 million production less than in 1941. Muskrat and several small fields declined, but in general the trend was upward.

Gross production amounted to 46,471 million cubic feet—a 7-percent gain over the 43,409 million produced in 1941. The most productive areas and quantities produced were: Salt Creek, 8,926 million cubic feet; Lance Creek, 7,917; South Baxter Basin, 5,784; Big Sand Draw,

5,652; Elk Basin, 2,241; and Garland, 2,101.

Only 716 million cubic feet of gas were lost in 1942, 1,404 million were used in the field, and 14,322 million were returned to formations, leaving 30,029 million to be marketed. Gas marketed was 6 percent more than the 28,317 million marketed in 1941 and 13 percent over the 1940 record. South Baxter Basin, with 5,774 million, and Big Sand Draw, with 5,652 million, led in volume of gas marketed, supplying over one-third of the total amount. Salt Creek, which ranked first in gross production, stood third in amount of gas marketed, with 2,744 million, and Lance Creek, second in gross production, ranked fourth with 2,141 million.

Repressuring was practiced in eight fields during the year. In Salt Creek 6,182, in Lance Creek 5,775, and in Wertz 1,172 million cubic feet of gas were returned to the sands. Comparatively small amounts were also injected in Rock Creek, Lost Soldier, Elk Basin, La Barge, and Grass Creek fields, bringing the total to 14,322 million—a gain of

almost 15 percent over the 1941 figure.

Salt Creek with 8,926, Lance Creek with 7,856, and Big Sand Draw with 5,652 million supplied 96 percent of the 23,254 million cubic feet of gas treated for natural gasoline. Rock Creek, Elk Basin, and Grass Creek supplied the other 4 percent. In 1941, 22,366 million feet were treated.

### CONSUMPTION

Consumption of natural gas in 1941 continued the upward trend evidenced since 1938, totaling 2,805,192 million cubic feet. This was a 6-percent gain over the peak of 2,654,659 million cubic feet attained in 1940. Increases over 1940 were made in all but five States. Domestic consumption declined 0.4 percent from 1940, although the number of consumers increased. The over-all gain was in the industrial load, as shown by an 18-percent increase in gas used by miscellaneous industrial consumers in 1941, largely owing to rapidly increasing demands from defense industries. The average value of total consumption increased 0.4 cent over the 1940 average to 22.1 cents a thousand cubic feet.

Ohio produced only 31 percent of the State requirements and ranked first in imports from other States. Texas again ranked first in amount consumed, followed by California, Louisiana, Oklahoma.

Pennsylvania, and Ohio in the order named.

## Natural gas consumed in the United States, 1937-41

			Domes	tic and cor	c and commercial consumption						
e de la companya de la companya de la companya de la companya de la companya de la companya de la companya de	Consum	ers (thous	ands) 1	Billio	ns of cubic	feet	Average number of	Average			
Year	Domes- tic	Com- mercial	Total	Domes- tic	Com- mercial	Total	M cubic feet used per domestic and commercial consumer	value at points of consumption per M cubic feet (cents)			
1937 1938 1939 1940	8, 348 8, 570 8, 888 9, 245 9, 730	680 695 715 741 767	9, 028 9, 265 9, 603 9, 986 10, 497	372 368 391 444 442	117 114 119 134 145	489 482 510 578 587	54. 2 52. 0 53. 1 57. 9 55. 9	67. 6 68. 3 67. 9 65. 7 65. 9			

		Industrial consumption								
		Billions of cubic feet								Aver-
Year	Field	Car- bon- black manu- facture	Petro- leum refin- eries	Elec- tric public- utility power plants 2	Port- land- cement plants 3	Other indus- trial	Total indus- trial	Average value at points of con- sump- tion per M cubic feet (cents)	Bil- lions of cubic feet	value at points of consumption per M cubic feet (cents)
1937. / 1938	651 659 681 712 686	341 325 347 369 365	113 110 98 128 148	171 170 191 183 205	41 37 40 42 54	597 511 607 643 760	1, 914 1, 812 1, 964 2, 077 2, 218	10. 3 9. 4 9. 6 9. 5 10. 5	2, 403 2, 294 2, 474 2, 655 2, 805	22. 0 21. 8 21. 6 21. 7 22. 1

<sup>&</sup>lt;sup>1</sup> Includes consumers served with mixed gas. <sup>2</sup> Chapters on Cement in Minerals Yearbook. <sup>2</sup> Federal Power Commission.

Natural gas consumed in the United States, 1937-41, by States, in millions of cubic feet

State	1937	1938	1939	1940	1941
Alabama	16, 593	14. 796	20, 093	23, 461	32, 023
Arizona	12, 857	12, 660	16, 643	18,002	18, 213
Arkansas	35, 074	34, 833	35, 673	39, 719	46, 933
California	329, 769	315, 168	348, 361	351, 950	374, 905
Colorado		19, 212	21, 978	22, 111	26, 574
Colorado District of Columbia	3, 458	3,826	4,069	4, 686	5, 124
Florida	1, 389	1, 469	1, 658	1, 481	2, 378
Georgia	13, 893	14, 783	16, 296	20, 551	23, 975
Illinois	78, 650	66, 500	77, 134	88, 088	98, 634
Indiana	23, 551	26, 706	30, 795	29, 214	29, 989
Iowa	21, 354	20, 109	21, 732	23, 460	24, 589
Kansas	96, 822	86, 105	85, 865	96, 772	109, 059
Kentucky	18, 154	15, 350	16, 563	18, 881	20, 170
Louisiana	174, 153	162, 260	164, 667	185, 089	222, 025
Maryland	1,011	1, 247	4, 907	5, 855	6, 587
Michigan	24, 112	24, 697	27, 316	32, 790	37, 290
Minnesota	13.111	14, 641	17, 262	19, 904	22, 672
Mississippi	13, 327	12, 785	14, 207	17, 657	20, 813
Missouri	46, 898	42, 505	47, 157	53, 141	58, 138
Montana	1 21, 594	1 18, 225	1 19, 765	22, 328	24, 751
Nebraska	17, 263	17, 539	19, 654		19, 205
New Mexico	28,056	32, 890	38, 981	20,087	
New York		47, 950		40, 198	39, 138
North Dakota		1, 533	46,877	27, 250	25, 384
Ohio		108, 013	1,607 114,720	1,725	1, 741
Oklahoma	269, 604			129, 856	136, 251
Pennsylvania	119, 501	244, 443 96, 285	231, 005	230, 806	209, 395
South Dakota	119, 501		109, 746	121, 230	139, 492
Tennessee	5, 519 13, 353	5, 354	5, 712	6, 454	6, 580
Texas.	10,000	14, 047	<sup>2</sup> 15, 558	16, 819	22, 495
II taas	. 706, 120	729, 603	796, 561	874, 294	875, 620
UtahVinginia	12, 449	11,699	13, 172	14,802	16, 667
Virginia	550	615	² 788	963	1, 166
Washington	143	117	63	36	1
West Virginia		57, 478	69, 394	77, 540	88, 597
Wyoming	I	18, 654	17, 786	17, 459	18, 618
Total United States	2, 403, 041	2, 294, 097	2, 473, 765	2, 654, 659	2, 805, 192

Includes natural gas piped from Canada.
 Small amount of gas consumed in Tennessee included with Virginia; separate figures not available.

Natural gas treated at natural-gasoline plants in the United States, 1937-41, by States, in millions of cubic feet

State	1937	1938	1939	1940	1941
Arkansas California Colorado Illinois Kansas Kentucky Louisiana Michigan Montana New Mexico New York Ohio Ohlahoma Pennsylvania Texas West Virginia	4, 031 381, 568 1, 53 1, 027 183, 416 34, 981 144, 474 1, 381 9, 062 61, 625 50 33, 625 338, 007 31, 508 754, 696 140, 512	21, 377 388, 187 145 1, 110 144, 631 38, 446 116, 331 1, 395 7, 126 97, 830 65 22, 488 265, 746 22, 600 752, 784 122, 301 17, 000	19, 171 377, 041 130 2, 440 141, 945 36, 817 114, 990 1, 019 8, 116 97, 010 65 32, 703 219, 755 26, 662 914, 701 140, 982 16, 483	26, 584 375, 407 142 12, 716 150, 963 39, 662 145, 234 1, 414 9, 528 101, 213 40 38, 547 219, 255 40, 161 1, 123, 236 168, 206 19, 092	19, 906 371, 350 134 23, 732 176, 088 38, 062 191, 194 3, 581 10, 386 105, 161 5 37, 546 200, 319 43, 704 1, 325, 471 195, 093 21, 568
Wyoming	2, 108, 800 88	2, 035, 562 89	2, 150, 000 87	2, 471, 400 93	2, 763, 300 99

Treated for natural gasoline.—The amount of natural gas processed for natural gasoline increased 12 percent, or from 2,471,400 million cubic feet in 1940 to 2,763,300 million in 1941. The ratio to total consumption was 99 in 1941 compared with 93 in 1940. Gas treated in Louisiana increased 32 percent and in Texas 18 percent over the 1940 volumes, largely because of increases in cycle-plant operations. The amount in Kansas increased 17 percent and in West Virginia 16 percent. In Oklahoma it decreased 9 percent and in California 1 percent.

Domestic and commercial.—Domestic consumers used 442,067 million cubic feet of natural gas in 1941, compared with 443,646 million in 1940. The number of consumers increased by 484,880 and totaled 9,730,110 in 1941. The decrease in consumption in the face of added meters is partly explained by higher average temperatures in 1941 over 1940 and may also represent a more frugal use of fuel following rising living costs. The average consumption per domestic consumer was 45,433 cubic feet in 1941 compared with 47,986 cubic feet in 1940. Commercial consumption increased 8 percent over 1940 to 144,844 million cubic feet.

The average value of domestic gas was 72.0 cents a thousand cubic feet in 1941 compared with 71.1 cents in 1940; the average of commer-

cial gas was 47.2 compared with 47.8.

# Domestic and commercial consumption of natural gas in the United States in 1941, by States 1

		Dome	estic			Comm	ercial			То	tal	
State	Consumers	M cubic feet	Value at p consum	oints of otion	Consumers	M cubic feet	Value at j	points of option	G	M cubic feet	Value at po	oints of ption
••••••••••••••••••••••••••••••••••••••			Total	Average (cents)	Consumers	WI CUDIC IEEU	Total	Average (cents)	Consumers	WI CUDIC 1660	Total	Average (cents)
Alabama Arizona Arizona Arizona Arizona Arkansas California Colorado District of Columbia Florida Georgia Illinois Indiana Iowa Kansas Kentucky Louisiana Maryland Michigan Minnesota Mississippi Missouri Montana Nebraska New Mexico New York North Dakota Ohio Oklahoma Pennsylvania South Dakota Tennessee Texas Utah Virginia Washington West Virginia Wyoming	38, 150 42, 000 78, 390 1, 799, 140 102, 480 (2) 4, 740 92, 990 1, 282, 220 141, 480 223, 740 179, 980 206, 370 244, 290 604, 620 174, 130 56, 820 417, 620 121, 090 25, 200 424, 200 (2) 1, 257, 010 263, 570 691, 110 17, 060 53, 690 697, 520 34, 110 (2) (3) (4) (2) (3) (4) (2) (4) (5) (6) (7) (9) (9) (1, 257, 520 (1, 257, 520 (2, 257, 520 (3, 257, 520 (4, 257, 520 (4, 257, 520 (5, 257, 520 (6, 257, 520 (7, 257, 520 (7, 257, 520 (8, 257, 520 (9,	1, 962, 000 1, 653, 000 6, 159, 000 80, 929, 000 6, 633, 000 (2) 162, 000 5, 571, 000 3, 800, 000 10, 488, 000 10, 488, 000 13, 515, 000 6, 151, 000 4, 008, 000 13, 515, 000 6, 543, 000 24, 716, 000 6, 543, 000 15, 997, 000 15, 997, 000 16, 997, 000 21, 405, 000 37, 412, 000 31, 424, 000 39, 478, 000 19, 984, 200 39, 478, 000 (2) 19, 984, 200 3, 230, 000	\$1, 974, 000 2, 014, 000 3, 082, 000 58, 791, 000 5, 085, 000 4, 742, 000 4, 536, 000 4, 4536, 000 4, 536, 000 24, 417, 000 4, 536, 000 24, 417, 000 24, 417, 000 24, 417, 000 24, 716, 000 20, 989, 000 25, 481, 000 21, 219, 000 3, 080, 000 4, 173, 000 11, 683, 000 11, 683, 000 11, 683, 000 12, 219, 000 23, 873, 000 96, 897, 000 24, 667, 000 27, 432, 000 27, 432, 000 27, 432, 000 29, 000, 600 (2) 7, 302, 400 1, 507, 000	100. 6 121. 8 50. 0 72. 6 76. 7 (2) 126. 5 85. 1 125. 5 119. 4 96. 65. 3 77. 4 96. 7 89. 1 86. 2 90. 4 47. 1 75. 5 65. 3 46. 3 67. 9 (3) 67. 9 (3) (3) (3) (46. 7	4, 320 4, 280 13, 180 103, 300 10, 000 (?) 530 7, 990 69, 230 10, 900 11, 080 22, 590 21, 1840 25, 643 36, 030 6, 320 8, 230 8, 230 8, 230 8, 230 115, 620 327, 880 11, 910 115, 620 327, 880 1, 910 12, 910 1	\$26,000 1,039,000 3,499,000 24,151,000 2,032,000 (2) 92,000 3,850,000 5,401,000 962,000 1,507,000 8,811,000 2,590,000 7,572,000 3,382,000 4,108,000 3,382,000 1,550,000 3,238,000 1,550,000 3,238,000 1,272,000 8,915,000 8,128,000 1,274,000 2,667,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000 1,274,000	\$423, 000 574, 000 10, 988, 000 1, 160, 000 69, 000 1, 341, 000 4, 888, 000 1, 001 1, 001 2, 538, 000 1, 261, 000 1, 261, 000 1, 261, 000 2, 537, 000 1, 150, 000 863, 000 2, 423, 000 2, 423, 000 2, 423, 000 2, 423, 000 2, 423, 000 2, 557, 000 1, 150, 000 863, 000 2, 557, 000 1, 150, 000 863, 000 2, 175, 000 521, 000 7, 175, 000 521, 000 7, 086, 000 2, 1715, 600 607, 000	51. 2 55. 2 36. 3 45. 5 57. 1 64. 1 34. 8 86. 8 87. 1 67. 0 34. 3 49. 1 33. 5 46. 9 88. 2 20. 7 56. 8 37. 1 57. 1 31. 5 58. 8 40. 9 31. 5 57. 1 31. 5 33. 4 33. 5 33. 5 33. 4 33. 5 33. 3 33. 3	42, 470 46, 280 91, 570 1, 902, 440 112, 480 (*) 1, 351, 450 206, 920 152, 560 1, 381, 450 250, 840 198, 060 229, 960 225, 6130 630, 260 225, 940 182, 840 65, 300 441, 810 52, 940 129, 320 1, 372, 630 295, 900 748, 990 18, 970 60, 450 776, 610 35, 680 (*) (*) (*) (*) (*) (*) (*) (*) (*) (*)	2, 788, 000 2, 692, 000 9, 658, 000 105, 080, 000 8, 665, 000 (2) 254, 000 9, 421, 000 9, 421, 000 6, 576, 000 11, 791, 000 18, 666, 000 27, 090, 000 26, 374, 000 17, 623, 000 17, 623, 000 17, 623, 000 17, 623, 000 17, 623, 000 17, 623, 000 17, 623, 000 17, 624, 000 19, 235, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 192, 000 25, 117, 000 25, 117, 000 55, 022, 000	\$2, 397, 000 2, 588, 000 4, 317, 000 69, 779, 000 6, 245, 000 6, 083, 000 29, 105, 000 5, 374, 000 6, 637, 000 6, 637, 000 24, 055, 000 24, 055, 000 3, 743, 000 14, 776, 000 4, 230, 000 15, 036, 000 22, 271, 000 16, 416, 000 23, 178, 000 14, 7842, 000 12, 708, 000 14, 7842, 000 12, 708, 000 13, 629, 000 34, 518, 000 24, 184, 000 25, 184, 000 26, 198, 000 27, 184, 000 29, 198, 000 29, 114, 000 29, 114, 000 20, 114, 000 20, 114, 000 20, 114, 000 20, 114, 000 20, 114, 000 20, 114, 000 20, 114, 000 20, 114, 000	. 86.0 96.1 44.7 66.4 72.1 (2) 103.9 64.6 117.1 112.9 89.8 56.3 54.3 55.9 57.5 60.6 83.8 40.6 71.5 57.0 85.3 (3) 85.3 (4) 85.3 (5) 85.3 (6) 85.3 (7) 85.5 8
Total: 1941 1940	9, 730, 110 9, 245, 230	442, 067, 000 443, 646, 000	318, 093, 000 315, 515, 000	72.0 71.1	766, 910 741, 020	144, 844, 000 134, 644, 000	68, 398, 000 64, 399, 000	47. 2 47. 8	10, 497, 020 9, 986, 250	586, 911, 000 578, 290, 000	386, 491, 000 379, 914, 000	65. 9 65. 7

<sup>&</sup>lt;sup>1</sup> Includes natural gas used with manufactured gas.

<sup>&</sup>lt;sup>3</sup> Maryland includes District of Columbia and Virginia.

<sup>3</sup> Utah includes North Dakota and Washington.

Field.—Gas used in the field totaled 686,158 million cubic feet in 1941 compared with 711,861 million in 1940. The apparent decline resulted from the use of a new basis of reporting by a company that has been the largest consumer in Texas. The amount actually consumed in the field in 1941 probably increased several percent over the 1940 total. The estimated value of gas used for field purposes was \$29,993,000 compared with \$27,158,000 in 1940. These figures indicate a gain of 0.6 cent a thousand cubic feet in 1941.

Carbon-black manufacture.—An increase in the proportion of high-yield carbon blacks manufactured, together with a 3-percent decline in total output, reduced the amount of gas used at carbon-black plants in 1941. The total declined 1 percent to 365,377 million cubic feet from 368,802 million in 1940. A gain of 0.1 cent was recorded in the average value, mainly because of a higher average in Texas. The total value was \$4,135,000 in 1941 compared with \$3,702,000 in 1940.

Petroleum refineries.—Petroleum refineries consumed 148,127 million cubic feet of natural gas in 1941—a 16-percent gain over the 128,007 million used in 1940. This was 18 percent of the total B. t. u. requirements of the industry in 1941—0.9 percent more than was supplied in 1940. As similar comparisons for fuel oil show a loss of 1.6 percent, it would appear that natural gas was used as a substitute for that fuel

at some refineries in 1941.

Electric public-utility power plants.—Requirements from public-utility power plants totaled 205,156 million cubic feet in 1941, a 12-percent gain over 1940. Of the major consuming States, sharp gains were noted in Louisiana, Texas, and Kansas, where gas was cheap. California used 13 percent less gas for this purpose in 1941 than in 1940, probably because of the increased use of water power. Tennessee and Arkansas reported sharp increases and Illinois a sharp decrease.

Portland-cement plants.—Consumption at portland-cement plants increased 29 percent to 54,208 million cubic feet in 1941 compared with 41,949 million in 1940. A very small percentage of the total fuel requirements of the industry is furnished by natural gas. However, as its proportion of the total increased slightly in 1941 and that of fuel oil decreased, it may be supposed that gas has displaced oil

in some cases.

Other industrial.—Natural gas used for "other" industrial purposes increased 25 percent between 1939 and 1941. It totaled 759,255 million cubic feet in 1941, 18 percent over the 642,594 million used in 1940. Gas used by this class of consumers was 27 percent of the total consumption in 1941 compared with 24 percent in 1940 and displaced field use for the first time in volume. Field use took 24 percent of the total consumption in 1941 compared with 27 percent in 1940.

Miscellaneous industrial consumption increased in all States but New York, Oklahoma, and South Dakota. California, the largest consumer in both years, gained 15 percent over 1940; Pennsylvania, second in rank, gained 33; and Louisiana, third, gained 10. These three States consumed one-third of the total gas used for miscellaneous

industrial purposes in 1941.

# Industrial consumption of natural gas in the United States in 1941, by States and uses

	Field (d pumping erating recovery	g, and op- gasoline-	Carbon-bl	ack manu	facture	Fuel at pe	Fuel at petroleum refineries, electric public-utility power plants, portland- cement plants, and other industrial					Total industrial			
State ·	-	Value at		Value at of consur	points nption		•	M cubic fe	et		Value at post of consum	points iption		Value at p	
	M cubic feet (esti- mated)	points of consump- tion (esti- mated)	M cubic feet	Total	Aver- age (cents)	Petro- leum re- fineries	Electric public- utility power plants	Portland- cement plants	Other in- dustrial	Total	Total	Aver- age (cents)	M cubic feet	Total	Average (cents)
Alabama							898, 000	(1)	1 28, 337, 000	29, 235, 000	\$4, 962, 000	17.0	29, 235, 000	\$4, 962, 000	17.0
Arizona							2, 293, 000		128, 337, 000 13, 228, 000	15, 521, 000	3, 123, 000	20.1	15, 521, 000	3, 123, 000	20.1
Arkansas	10, 417, 000	\$613,000				4, 669, 000	5, 262, 000	(1)	116, 927, 000	26, 858, 000	2,863,000	10.7	15, 521, 000 37, 275, 000	3, 476, 000	9.3
Arizona Arkansas California Colorado District of Co-	127, 466, 000	7, 740, 000				20, 073, 000	12, 153, 000	11, 822, 000	98, 311, 000	142, 359, 000	19, 154, 000	13.5	<b>269, 825, 000</b>	<b>26</b> , 894, 000	10.0
Colorado	200,000	11,000	<u>-</u>			2,000	749,000	(1)	116, 958, 000	17, 709, 000	2, 727, 000	15.4	17, 909, 000	2, 738, 000	15.3
District of Co-	ì	1													
lumbia									(2)	(2)	(2) 335,000	(2)	(2)	(2)	(2)
Colorado District of Co- lumbia Florida Georgia Illinois Indiana Iowa Kansas Kentucky Louisiana									2, 124, 000	2, 124, 000	335,000	15.8	2, 124, 000	335,000	15.8
Georgia		972 000					5, 746, 000		8, 808, 000	14, 554, 000	2, 630, 000 13, 860, 000	18.1	14, 554, 000 73, 775, 000	2, 630, 000	18.1
Indiana	8, 999, 000	273,000				241,000	2, 485, 000		10, 50, 000	64, 776, 000	13,860,000	21.4	73, 775, 000	14, 133, 000	19.2
Torro	991,000	19,000					5 979 000	(1)	110, 500, 000	24, 846, 000	6, 221, 000	25. 0 16. 2	25, 227, 000	6, 240, 500	24.7
Kancac	10 593 000	1 345 000	(3)	(8)	(3)	5 139 000	10 466 000	7 645 000	320 952 000	24, 846, 000 18, 014, 000 8 63, 102, 000 6, 488, 000 122, 494, 000	2, 923, 000	\$ 12. 4	18, 014, 000	2, 923, 000 9, 165, 000	16.2
Kentucky	1 801 000	257 000	. 6	()	(9)	0, 100, 000	10, 400, 000	7, 040, 000	6 488 000	6 499 000	1 814 000	28.0	82, 685, 000 8, 379, 000	2, 071, 000	
Louisiana	62 844 000	1.998,000	18 627 000	\$576 000	3 1	23 967 000	33 493 000	(1)	165 034 000	122 404 000	12 707 000	10.4	203, 965, 000	15, 281, 000	
Maryland	02,011,000	2,000,000	20,021,000	40.0,000		20,001,000	00, 100, 000		2 5, 787, 000	122, 494, 000 2 5, 787, 000	2 1, 684, 000	2 29. 1	<sup>2</sup> 5, 787, 000	<sup>2</sup> 1, 684, 000	2 29.1
Michigan	1, 534, 000	123,000				103,000	17,000		10, 444, 000	10, 564, 000	5, 306, 000	50. 2	12,098,000	5, 429, 000	
Minnesota							2, 672, 000		11, 146, 000	13, 818, 000 12, 621, <b>0</b> 00	2, 559, 000	18.5	13, 818, 000	2, 559, 000	
Mississippi	802,000	37,000					1, 754, 000		10, 867, 000	12, 621, 000	1,862,000		13, 423, 000	1,899,000	14.1
Missouri	520,000	83,000					12, 271, 000	(1)	1 27, 724, 000	39, 995, 000	7, 185, 000		40, 515, 000	7, 268, 000	17.9
Montana	1, 223, 000	69,000				926, 000	984, 000		11, 207, 000	13, 117, 000	1,779,000	13.6	14, 340, 000	1,848,000	
Nebraska							4, 928, 000	(1)	1 7, 229, 000	12, 157, 000	2,073,000	17.1	12, 157, 000	2, 073, 000	
New Mexico	20, 835, 000	421,000				44,000	4, 125, 000		10, 147, 000	14, 316, 000	1, 982, 000	13.8	35, 151, 000	2, 403, 000	6.8
New 10rk	324,000	82,000				92,000	28,000		5, 705, 000	5, 825, 000 (4)	3, 090, 000				
Ohio	1 575 000	270 000				1 000	1 735 000		50 007 000	EU 633 UUU	21 067 000	(4) 35, 2	(4)	01 227 000	(4) 34.7
Oklahoma	116, 858, 000	3, 554, 500	(3)	(3)	(8)	11. 034, 000	12 945 000	(1)	1838 238 000	59, 833, 000 62, 217, 000 87, 427, 000 4, 054, 000	8 5 078 000	3 8. 2	179, 075, 000	21, 337, 000 8, 632, 500	4.8
Pennsylvania	6, 525, 000	1, 621, 000				944, 000	11,000		86, 472, 000	87, 427, 000	27, 029, 000	30. 9	93, 952, 000	28, 650, 000	30.5
South Dakota							1, 353, 000	(1)	1 2, 701, 000	4, 054, 000	739,000	18. 2	4, 054, 000	739, 000	18.2
Tennessee							8, 137, 000		8, 267, 000	16, 404, 000	2, 750, 000	16.8		2, 750, 000	16.8
Kentucky Louisiana Maryland Michigan Michigan Mississippi Missouri Montana Nebraska New Mexico New York North Dakota Ohio Oklahoma Pennsylvania South Dakota South Dakota Tennessee Texas Utah	282, 011, 000	8, 693, 000	330, 351, 000	3, 263, 000	1.0	76, 439, 000	60, 059, 000	12, 935, 000	58, 206, 000	207, 639, 000	21, 627, 000	10.4	820, 901, 000	33, 583, 000	4.1
Utah	29,000	1,000				110,000	4 256, 000	(1)	413, 990, 000	14, 356, 000	4 1, 755, 000	4 12. 2	4 14, 385, 000	4 1, 756, 000	4 12.

Wirginia         14, 649,000         2, 503,000           Wyoming         7, 492,000         279,000           Misoellaneous         **16, 399	3 298, 000	783, 000 3, 561, 000	16,000 707,000 	(2) 48, 032, 000 1, 836, 000		2) (2) 21. 0 63, 480, 000 12. 3 13, 596, 000	20. 1 7. 6
Total: 1941. 686, 158, 000 29, 993, 000 365, 377 711, 861, 000 27, 158, 000 368, 802	000 4, 135, 000 000 3, 702, 000		205, 156, 000 54, 208, 000 183, 156, 000 41, 949, 000			17. 1 2, 218, 281, 000 16. 7 2, 076, 369, 000	

<sup>1</sup> Gas used in portland-cement plants included under "Miscellaneous" for United States total and under "Other industrial" for State total to avoid disclosing figures of individual

operators.

Maryland includes District of Columbia and Virginia.

Gas used in carbon-black manufacture included under "Miscellaneous" for United States total and under "Other industrial" for State total to avoid disclosing figures of individual operators.

4 Utah includes North Dakota.

The average value of the gas consumed at petroleum refineries, electric public-utility power plants, and portland-cement plants, and for "Other" industrial purposes was 17.1 cents in 1941 compared with 16.7 cents in 1940. This 0.4-cent gain may be attributed to large gains in volume in some of the Eastern States, where high prices prevail.

Mixed gas.—The use of natural gas mixed with manufactured gas increased 1 percent in 1941 over 1940. The total volumes were 65,979 million cubic feet in 1941 and 65,102 million in 1940. Illinois, which has been the largest consumer of mixed gas, and New York, next in rank, both decreased about 1 percent in the quantity of natural gas blended. The number of consumers increased in most States. The total number of domestic and commercial consumers was 2,619,100 in 1941 compared with 2,514,910 in 1940. Natural gas used in mixed gas was valued at \$56,952,000 compared with \$56,202,000 in 1940. The average value remained unchanged at 86.3 cents per 1,000 cubic feet.

Consumption of natural gas used with manufactured gas in the United States in 1941, by States

	Dor	nestic	Com	nercial		То	tal
State	Consum- ers	M cubic feet	Consum- ers	M cubic feet	Industrial (M cubic feet)	M cubic feet	Value at points of consumption
District of Columbia Illinois Indiana Iowa Kentucky Maryland Minnesota Missouri Nebraska New York Ohio Pennsylvania Virginia	169, 910 1, 113, 640 59, 150 56, 660 79, 910 24, 990 144, 970 245, 56 56, 110 283, 460 163, 890 56, 150 24, 890	4, 044, 000 15, 587, 000 513, 000 1, 388, 000 2, 912, 000 689, 000 4, 163, 000 1, 243, 000 1, 243, 000 1, 530, 000 349, 000	8, 370 57, 310 2, 890 3, 860 7, 430 450 5, 800 11, 760 12, 220 16, 060 2, 730 680	561, 000 4, 465, 000 154, 000 243, 000 1, 049, 000 25, 000 646, 000 729, 000 63, 000 1, 240, 000 245, 000 299, 000 44, 000	519,000 5,633,000 296,000 96,000 1,241,000 10,000 496,000 1,823,000 208,000 251,000 16,000	5, 124, 000 25, 685, 000 963, 500 1, 697, 000 5, 202, 000 4, 816, 000 5, 408, 000 11, 249, 000 1, 153, 000 2, 080, 000 409, 000	\$3, 552, 000 25, 397, 000 878, 000 1, 693, 000 2, 852, 000 4, 417, 000 5, 453, 000 886, 000 8, 739, 000 690, 000 1, 367, 000 416, 000
Total: 1941 1940	2, 479, 210 2, 377, 760	45, 454, 000 45, 670, 000	139, 890 137, 150	9, 763, 000 9, 610, 000	10, 762, 000 9, 822, 000	65, 979, 000 65, 102, 000	56, 952, 000 56, 202, 000

## INTERSTATE SHIPMENTS

Interstate shipments totaled 815,672 million cubic feet in 1941—a 10-percent increase over 1940. Gas was transported from 21 States in 1941.

New shipments were reported from Arkansas to Louisiana and Texas. Some Texas gas was turned into the pipe line serving Alabama, Georgia, and Mississippi. The States that transported the largest volumes of interstate gas in 1941 were Texas, Louisiana, and West Virginia in the order named. Sharp decreases were noted in New York and Mississippi. Industries in Pennsylvania that formerly drew their natural-gas supplies from New York are now using West Virginia and Kentucky gas. Texas supplied 32 percent of the total shipments in 1941, Louisiana 24, and West Virginia 17, the same proportions as in 1940. Shipments from Pennsylvania to New York continued the recession started in 1940.

# Interstate transportation of natural gas in 1941 1

State from which gas was transported	State through which gas was transported	State to which gas was trans- ported	M cubic feet
Arkansas		Louisiana	4,026,000
21114411949-1-1-1-1-1-1-1-1-1-1-1-1-1-1-1		Texas	204,000
			4, 230, 000
Colorado	Wyoming	Utah	2, 806, 000
		Wyoming	2, 930, 000
Illinois	Indiana	Indiana Kentucky	199,000 515,000
	111111111111111111111111111111111111111		714,000
Indiana		Illinois	53,000
inulana		Kentucky	398,000
		Ohio	1,000
***			452,000
Kansas		Colorado	667,000
	Missourido	Illinois	2, 760, 000
	Illinois	Indiana	5, 089, 000
	Nebraska	Iowa	6, 973, 000
	South Dakota	}do	16,00
	Missouri	l)	-
	IllinoisIndiana	Michigan	7, 167, 000
	Ohio	]]	
	Nebraska	Minnesota	8, 583, 000
	Iowa	Missouri	12, 776, 000
		Nebraska	8, 544, 000
•	Nebraska Iowa	}do	4,000
	Missouri	ik	1.0
	Illinois	Ohio	42,000
	Indiana	Oklahoma	617,000
	Nebraska	South Dakota	1,040,000
			54, 278, 000
Kentucky	West Virginia	h	
	Virginia	District of Columbia	5, 124, 000
	Maryland	Indiana	106,000
	West Virginia	Maryland	4, 682, 00
	Virginia		2, 002, 00
	Virginia Virginia	do	749 00
	Virginia Maryland	ao	743, 00
•	District of Columbia	Ohio	3, 297, 000
	West Virginia	.]do	5,009,000
	do	Pennsylvania	17, 187, 000 688, 000
	do	Virginia	000,000
	Virginia	}do	409,00
	Maryland		200,000
	District of Columbia	West Virginia	15, 691, 00
			52, 936, 000
Louisiana	Mississippi	Alabama	30, 692, 000
110dmmm		Arkansas	24, 975, 000
	Mississippi Alabama	Florida	2, 157, 000
	Mississippi	Georgia	02 100 00
	Alabama	Georgia	23, 188, 000
	Arkansas Missouri		21, 648, 00
		Mississippi	14, 972, 00
	Arkansas	Missouri	2, 378, 00 12, 173, 00
	do	.h · ·	14, 110, 00
	Missouri	[ }do	6, 244, 00
	Illinois		
	Arkansas	Tennessee	22, 448, 00
		Texas	34, 570, 00
	Arkansas	. do	1, 335, 00
	Alkansas	1	196, 780, 0

<sup>&</sup>lt;sup>1</sup> Includes exports to Canada and Mexico.

# Interstate transportation of natural gas in 1941—Continued

State from which gas	State through which gas was	State to which gas was trans-	M cubic
was transported	transported	ported	feet
Mississippi		Alabama	425, 000
	Alabama	FloridaLouisiana	221, 000 350, 000
		Louisiana	
			996, 000
Missouri		Illinois	8, 000 16, 000
	Illinois	.13	16,000
	Indiana	Michigan	22,000
end of the	Ohio	P	
			46,000
Montana		North Dakota	1, 741, 000
	North Dakota	South Dakota	1, 741, 000 3, 775, 000
			5, 516, 000
New Mexico	Texas		
INGM INTEXICOTTTTTTT	New Mexico	Arizona	18, 213, 000
	1	Colorado	206,000
	Texas New Mexico	Mexico	1, 154, 000
	Arizona	11	Ψ.
		Texas	7, 483, 000
			27, 056, 000
New York		Canada	27, 000 1, 958, 000
		Pennsylvania	1, 958, 000
			1, 985, 000
North Dakota	Montana   North Dakota	South Dakota	47,000
		1	
Ohio		Indiana West Virginia	4,000 96,000
		West viiginia	
			100,000
Oklahoma		Arkansas	1, 464, 000
	Kansas Missouri	}Illinois	88,000
	Kansas	1i_	
	Missouri Illinois	Indiana	163,000
	Kansas	lowa	1, 568, 000
	Nebraska Kansas	\\ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \	1,000,000
	Nebraska	}do	3,000
	South Dakota	Kansas	20, 663, 000
	Kansas	Lausas	20, 000, 000
	Missouri Illinois	   Michigan	228,000
	Indiana		223,000
	Ohio Kansas	1	
	Nebraska	Minnesota	1,926,000
	Iowa Kansas	Missouri	8 180 000
	do	Nebraska	8, 180, 000 1, 451, 000
	Nebraska	}do	1,000
	Iowa	}	1,000
	Kansas Missouri	]	
	Illinois	Ohio	1,000
	Indiana Kansas	ĮĮ.	
	Nebraska	South Dakota	234,000
		Texas	3, 007, 000
			38, 977, 000
Donnarimoni-	Now York	Canada	صنحند
Pennsylvania	New York	Canada	94,000 16,913,000 69,000
		Ohio	69,000
	West Virginia	West Virginia	450,000 3,510,000
•			
		]	21, 036, 000
•	•		

Interstate transportation of natural gas in 1941—Continued

Louisiana   Mississippi	906, 000 769, 000 4, 807, 000 25, 358, 000 787, 000 6, 145, 000 58, 593, 000 11, 332, 000
Mississippi	769, 000 4, 807, 000 25, 358, 000 787, 000 6, 145, 000 58, 593, 000
Louisiana	4, 807, 000 25, 358, 000 787, 000 6, 145, 000 58, 593, 000
New Mexico	25, 358, 000 787, 000 6, 145, 000 58, 593, 000
Louisiana	787, 000 6, 145, 000 58, 593, 000
Mississippi	6, 145, 000 58, 593, 000
Alabama	58, 593, 000
Oklahoma	58, 593, 000
Missouri Oklahoma Kansas Nebraska Iowa Oklahoma Kansas Missouri Illinois Oklahoma Kansas Nebraska Iowa  Illinois Oklahoma Iowa Iowa Iowa Iowa	58, 593, 000
Oklahoma  Kansas  Oklahoma  Ilowa Oklahoma  Kansas  Missouri Illinois Oklahoma  Kansas  Nebraska  Nebraska  Iowa  Ilowa	
Kansas	
Nebraska	
Iowa_	11, 332, 000
Oklahoma	11, 332, 000
Kansas	11, 332, 000
Missouri	
Illinois	
Kansas	1
Nebraska	
Iowa	12, 010, 900
10wa	,,
Illinois]	
Oklahoma	10 000 000
Kansas	16, 006, 000
Nebraska	
Oklahoma	1
Kansas	23,000
NebraskaSouth Dakota	
OklahomaKansas	31, 553, 000 10, 574, 000
Louisiana	10, 574, 000
Mexico	6, 191, 000
Oklahoma	
Kansas	
Missouri   Michigan	15, 957, 000
InnoisIndiana	ŀ
Ohio	
Oklahoma	
Kansas Minnesota	12, 163, 000
Nehraska	
Iowa	191,00
Oklahoma   Missouri	18, 615, 00
Oklahoma	7, 832, 00
Kansas	
Oklahoma	
Kansas	5,00
Nebraska	
IowaNew Mexico	1, 539, 00
Oklahoma	
Kansas	
Missouri	95, 00
Illinois.	
Indiana	13, 701, 00
	10, 101, 00
Oklahoma	1, 477, 00
Nebraska	
	662,00
New Mexico  Wyoming	002, 00
	257, 291, 00
Utahdo	216, 00
Tennessee	37, 00
	3. 126.00
Vantuaby	1. 162, 00
West Virginia Kentucky Maryland	81, 599, 00
West Virginia Kentucky Maryland Maryland Ohio	
West Virginia Kentucky Maryland Ohio Ohio do do Maryland	3, 930, 00
West Virginia Kentucky Maryland Ohio Ohio Pennsylvania	3, 930, 00 48, 337, 00
	3, 930, 00 48, 337, 00 227, 00
West Virginia Kentucky Maryland Ohio Ohio Pennsylvania	3, 930, 00 48, 337, 00 227, 00 138, 381, 00
	138, 381, 00
	3, 930, 00 48, 337, 00 227, 00 138, 381, 00
	138, 381, 0
West Virginia	138, 381, 00
	138, 381, 00 17, 00 1, 768, 00 1, 368, 00

## PIPE-LINE DEVELOPMENTS

Because of the steel shortage, the construction of gas lines came under strict supervision of the War Production Board. The relatively more urgent need for pipe-line expansion in crude oil led to the conversion of some gas-line mileage to oil lines as part of the several projects supervised by the Petroleum Administration for War. The net gain in gas-line mileage was therefore small—possibly smaller

than for any year since before the boom period, 1928-30.

Permission was granted to remove pipe from the Rodessa loop. After reconditioning, part of the line was to be relaid to meet the increased demand in the Dallas-Fort Worth area. In February a 139-mile line was started from the South Arkansas gas fields near Columbia to supply gas to two plants. The gas is sour, and desulfurization plants were built to make it marketable. The fields in Southern Arkansas were also the starting point for an 18-inch line to Little Rock and other communities in the central part of the State.

The Federal Power Commission granted permission for the Border Pipe Line Co. to build a line from the San Salvador fields in Hidalgo County, Tex. Plans for a 772-mile line from the Louisiana and Texas gas fields to Ohio, Pennsylvania, and West Virginia were considered but were still under advisement at the end of the year. The Lone Star Gas Co. started a line from Groesbeck to connect with the 18-inch main line at Buffalo. The Natural Gas Pipe Line Co. of America duplicated its 800-mile line of 24-inch pipe with 26-inch pipe to transport more gas from the Panhandle. A 12-inch line was laid from the Chickasha and Cement gas fields in Oklahoma to an Army cantonment. A 12-inch line between Manchester and Kalamazoo, Mich., was started in September 1942. A permit was granted for a 275-mile trunk line from Ohio to Kalamazoo. The line from the Lirrette gas field in Louisiana to Mobile was put in operation in February 1942 to supplement the line from Jackson.

## NATURAL GASOLINE

#### AND LIQUEFIED PETROLEUM GASES 1

By G. R. HOPKINS AND A. T. COUMBE 2

#### SUMMARY OUTLINE

	Page !	Natural gasoline—Continued.	Page
Natural gasoline		Stocks	1170
Summary			1170
Salient statistics		Cycling plants	1170
Prices and market conditions	1162	Yields	1171
Production			
Consumption and movements			1171
Refinery utilization			
"Direct" sales	1170	Liquefied petroleum gases	1172

#### NATURAL GASOLINE

#### SUMMARY

The natural-gasoline industry experienced a satisfactory year in 1942 in point of volume. The total output of all the light products—natural gasoline, cycle products, and liquefied petroleum gas—reached the record-breaking total of 3,509,814,000 gallons or 3 percent above 1941. However, this showing was due mainly to expanded cycle operations, as the output of natural gasoline alone was 8 percent below 1941.

Prices of natural gasoline were favored by starting the year well above the corresponding levels of 1941, but owing to price ceilings and transportation difficulties the trend in 1942 was generally downward. The average price for 26-70 grade in 1942 was 3.22 cents per gallon

compared with 3.70 cents in 1941.

As with production, the trend in stocks in 1942 depends on the products that are considered. Including liquefied petroleum gas, the trend was upward, but for natural gasoline and cycle products there was a decline. In any event, the pronounced draft on stocks that characterized 1941 was not repeated, which was probably another

reason for the price weakening.

Participation in the war program was a primary consideration of the industry in 1942. This participation took many forms, depending on products made, size, and location. Probably the most important roles were as suppliers of materials for aviation gasoline and rubber. Of these, aviation gasoline was by far the larger in volume. The liquefied-gas branch of the industry performed admirably in supplying fractions, mainly isobutane and isopentane, for aviation-gasoline manufacture, in addition to assuming added responsibilities for supplying certain war plants with fuels.

Data for 1942 are preliminary; detailed statistics with final revisions will be released later.
Tables compiled by E. M. Seeley, Petroleum Economics Division, Bureau of Mines.

The shortage of materials prevented much expansion in capacity. Losses in manpower were serious but not crippling. Ordinary research slowed, but much was learned as to the use of the light fractions in aviation gasoline and various chemicals, which should reduce the dependence of the industry on ordinary refinery blending in the postwar period.

Salient statistics of the natural-gasoline industry in the United States, 1938-42, in thousands of gallons

	1938	1939	1940	1941	1942 1
Production: Natural gasoline Cycle products Liquefied petroleum gases:	2, 156, 574	2, 169, 300	2, 339, 400	2, 208, 360 480, 354	2, 042, 502 665, 532
Isobutane at natural-gasoline and cycle plantsLiquefied petroleum gases at natural-	(2)	(2)	(2)	127, 932	118, 188
gasoline and cycle plants Liquefied refinery gases at refineries	(2) (2)	(2) (2)	(2) (2)	579, 264 199, 038	683, 592 192, 234
Total	2, 156, 574	2, 169, 300	2, 339, 400	3, 594, 948	3, 702, 048
Stocks, end of year: Natural gasoline	202, 860	185, 682	239, 568	{ 171, 276 8, 274	157, 3 <b>7</b> 4 13, 524
Liquefied petroleum gases Liquefied refinery gases	(2) (2)	(2) (2)	(2) (2)	6, 804 5, 376	23, 646 8, 946
Total	202, 860	185, 682	239, 568	8 179, 550 191, 730	203, 490
Demand: Used at refineries Jobbers, retailers, etc Sales of liquefied petroleum gases and	1, 678, 362 177, 240	1, 663, 452 171, 066	1, 660, 974 283, 290	2, 008, 650 837, 858	2, 391, 018 415, 800
liquefied refinery gases Exports and losses	165, 201 267, 948	223, 580 351, 960	313, 456 341, 250	462, 840 345, 618	4 490, 854 392, 616
Total	2, 288, 751	2, 410, 058	2, 598, 970	3, 654, 966	3, 690, 288
Value at plants:  Natural gasolinethousands of dollars Cycle products	87, 266 (2) 4. 0 2, 035, 562	90, 050 (2) 4. 2 2, 150, 000	68, 261 (2) 2. 9 2, 471, 400	88, 877 16, 938 13, 305 3, 5 2, 763, 300	78, 800 23, 200 19, 000 3, 4 \$3, 000, 000
feetgallons Average yield, all light productsdo	1. 06 (2)	1. 01 (2)	0. 95 (2)	0. 97 1. 23	\$ 0.90

## PRICES AND MARKET CONDITIONS

Although most spot prices for natural gasoline opened 1942 well above those for 1941, the decline beginning in February and reaching its lowest level in March brought prices below the 1941 average. The result was that the average for the 26-70 grade in Oklahoma, used as the market indicator, declined from 3.70 cents per gallon in 1941 to 3.22 cents in 1942. However, as the fluctuation in spot prices invariably is more pronounced than changes in the national average, the decline for the national average is estimated at 3.9 cents per gallon in 1941 to 3.8 cents in 1942. As indicated in figure 1, the downward movement in natural gasoline was contrary to the trend in the representative refinery-gasoline price (Oklahoma) used.

Subject to revision.
 Not available.
 For comparison with 1940.

<sup>4</sup> Preliminary total excluding most of the chemical use. See discussion on Liquefied Petroleum Gases at the end of this chapter.

Estimated.

However, the divergence in the trends was not enough to justify the feeling that the general relationship between these two prices has been greatly disturbed. The increase in natural-gasoline stocks at plants (see fig. 1) may have had something to do with the lower quotations; likewise, the decline in finished gasoline stocks may have influenced prices upward in spite of price ceilings.




FIGURE 1.—Trends in average value of natural gasoline, spot price of gasoline, and stocks of natural gasoline, 1918-42.

Prices to blenders of Mid-Continent natural gasoline, grade 26-70, with dates of price changes in 1942 and monthly and yearly average in cents per gallon

		Illational Legioleum	1101101		
Date	Cents	Date	Cents	Date	Cents
Jan. 1	5. 13	Mar. 24	2. 25	June 30	2. 50
24		25	2. 25-2. 38 2. 38	Average	2, 38
26		27	2. 25-2. 38	·	
27		31		July 8	2, 50-2, 60
28		01		9	2, 50
30		Average	2. 26	10	2, 50-2, 63
00				14	2.50
Average	4.94	Apr. 1	2.38	15	
		2	2. 25-2. 38	18 25	
Feb. 2		3	2, 38 2, 25-2, 38	25	
3		6	2. 20-2. 38	28	3.00
4		8	2, 25-2, 38	31	3. 13
5 7	3 75-4 00	10	2.38		
9		11	2, 25-2, 38	Average	2.69
10	3,50	13	2.38		3, 13-3, 38
11	3,38	15	2, 25-2, 38	Aug. 3	
13	3. 25-3. 38	17	2. 25	4	
14		18	2. 38 2. 25-2. 38	6	
16	3.00-3.13	20		14	
17 18	2. 75-3. 13 2. 75	24	2, 25	1	
19		27	2, 25-2, 38	Average	3, 0
20		29	2.38	September: Average	3.63
21	2, 25			Deptember: 111014ge-1	
24	2.38	Average	2.33	October: Average	3.6
25		35 . 4	2, 25-2, 50		
27	2. 25	May 4	2. 25-2. 30	Nov. 3	3.7
A =========	3, 09	22	2, 38-2, 50	6	
Average	3.00	28	2, 38	A verage	3.8
Mar. 5	2, 25-2, 38	29	2.38-2.50		
6	_ 2.25			December: Average	3.8
16	2, 25-2, 38	Average	2, 39	Average: 1942	3, 2
17	2, 25	-	2,38	Average: 1942	3.7
23	2.00-2.25	June 1	2.38	1911	3. 1

### [National Petroleum News]

#### PRODUCTION

Trends in total output.—The output of natural gasoline and cycle products trended upward in 1942, but crude-oil production decreased (see fig. 2). In relative terms, the gain in natural gasoline and cycle products was 1 percent and the loss in crude oil 1 percent. However, when cycle production, which has no direct relationship to crude-oil operations, is eliminated the curve for natural gasoline alone declines 8 percent. Part of the reason for this large decrease is that an increasing amount of lighter fractions of natural gasoline is being produced as liquefied petroleum gas.

The trend of the total output of light products (natural gasoline, cycle products, and liquefied gas) in 1942 was similar to crude oil in that both were downward from January to April but upward for the next 4 months. From then on the output of light products was up-

ward, but the course for crude oil flattened.




FIGURE 2.—Annual production of natural gasoline and crude petroleum, 1911-42.

Natural gasoline and cycle products produced in the United States, 1938-42, by
States, in thousands of gallons

						as of gai				
Year	Arkan- sas	Califor- nia	Colo- rado	Illinois	Kansas	Ken- tucky	Louisi- ana	Mich- igan	Mon- tana	New Mexico
1938 1939 1940 1941 1942 1	25, 648 24, 634 32, 096 28, 108 33, 523	607, 237 587, 476 577, 127	390 380 390	4.012	62, 175 64, 691 72, 876	7, 785 9, 539 10, 247	94, 090 113, 741	2, 971 3, 919 5, 670	2, 161 2, 603 2, 517	54, 707 55, 713 69, 115
									Total	
Year	New York	Ohio	Okla- homa	Penn- syl-	Texas	West Vir-	Wyo-		Value s	t plant
				vania		ginia	ming 3	Thou- sands of gallons <sup>3</sup>	Thou- sands of dollars	Aver- age per gallon (cents)
1938 1939 1940	27 34 17	7, 382 7, 445 8, 062	468, 499 436, 123 399, 369	10, 734 11, 756 15, 371	770, 047	50, 398 52, 272	30, 647 31, 461	2, 156, 574 2, 169, 300	90, 050	4. 0 4. 2
1941 1942 <sup>1</sup>	17 17 15	8, 217 6, 311	362, 247 345, 345	15, 440 15, 114	932, 040 1, 180, 221 1, 188, 352	58, 782 65, 873 71, 922	34, 102 34, 728 33, 675	2, 339, 400 2, 688, 714 2, 708, 034		2. 9 3. 9 4 3. 8

<sup>1</sup> Subject to revision.

<sup>&</sup>lt;sup>2</sup> Includes Utah in each year.
<sup>3</sup> Includes Cycle products as follows—1938: 1,259,000 gallons; 1939: 39,354,000 gallons; 1940: 165,690,000 gallons; 1941: 480,354,000 gallons; 1942: 665,532,000 gallons.

<sup>4</sup> Estimated.

California.—Natural-gasoline production continued to decline in California, as the total of 545,437,000 gallons was 5 percent below 1941. As in 1941, the decline was due to a further drop in the Kettleman Hills field. Output in the old Los Angeles Basin fields continued to hold up exceptionally well, and some of them—like Huntington Beach—made gains.

Monthly production of natural gasoline and allied products in the United States, 1941-42, by fields, in millions of gallons

Field	Jan.	Feb.	Mar.	Apr.	May	June	July	Aug.	Sept.	Oct.	Nov.	Dec.	Total
1941													
W. New York and W. Penn- sylvania. West Virginia. Ohio. Illinois. Kentucky. Michigan Kansas. Oklahoma.	1.6 9.4 .8 6.6 3.3 .5 8.0 37.7	1.4 8.7 .7 6.0 3.1 .5 7.7 34.1	1.6 9.2 .8 7.0 2.9 .5 7.4 37.5	1.3 7.5 .7 6.9 2.5 .5 6.7 36.6	1. 2 7. 5 .6 7. 3 2. 7 .5 6. 5 37. 1	0.9 6.9 7.3 2.4 6.2 36.4	0.9 6.6 .5 7.7 2.4 .5 6.3 37.1	1.0 6.9 .5 8.0 2.7 .4 6.4 38.5	1.2 6.9 .7 8.0 2.8 .5 6.7 38.8	1.4 8.3 .9 9.0 3.3 .5 7.5 40.3	1.7 9.8 .7 9.4 3.5 .4 8.0 39.7	1. 8 10. 3 . 8 10. 0 3. 8 . 4 8. 3 39. 6	16. 0 98. 0 8. 2 93. 2 35. 4 5. 7 85. 7
Texas: Gulf East Texas Panhandle Rest of States	17. 3 22. 9 35. 2 40. 1	16. 7 21. 2 35. 1 36. 6	17. 8 23. 3 35. 3 40. 3	18. 4 23. 7 35. 7 43. 3	19. 8 25. 8 36. 5 45. 8	21. 2 25. 1 34. 7 44. 5	23. 5 25. 6 35. 5 45. 7	24. 5 26. 6 36. 5 48. 0	24. 8 26. 1 37. 6 48. 8	28. 0 27. 1 39. 8 50. 1	28. 7 26. 0 39. 8 50. 0	29. 7 27. 0 40. 6 52. 5	270. 4 300. 4 442. 3 545. 7
Total Texas	115. 5 2. 8	109. 6 2. 5	116. 7 2. 8	121. 1 2. 8	127. 9 2. 9	125. 5 2. 8	130. 3 2. 9	135. 6 2. 8	137. 3 2. 8	145. 0 3. 2	144. 5 3. 1	149. 8 3. 0	1, 558. 8 34. 4
Louisiana: Gulf Inland	4.1 8.0	3. 6 8. 1	4.7 8.1	4. 7 7. 6	4. 9 7. 0	4.8 7.3	5. 5 17. 1	5. 6 17. 4	5. 2 19. 7	5. 9 20. 1	6. 2 21. 9	6. 6 21. 6	61. 8 163. 9
Total Louisiana New Mexico Montana Colorado, Utah, and Wyo-	12.1 6.1 .4	11.7 5.5 .4	12.8 6.2 .4	12.3 6.6 .3	11.9 7.0 .3	12.1 7.1 .3	22.6 •7.3 •3	23. 0 7. 3 . 3	24.9 7.0 .3	26.0 6.8 .3	28. 1 6. 9 . 4	28. 2 7. 2 . 3	225. 7 81. 0 4. 0
ming California	3. 2 55. 6	2, 8 50, 7	3.0 54.1	2.8 52.8	3. 1 55. 5	2. 8 53. 9	3.0 56.0	3. 0 56. 2	3.0 55.5	3.3 57.2	3. 4 55. 4	3. 3 56. 8	36. 7 659. 7
Total United States Daily average	263. 6 8. 5		262. 9 8. 5	261. 4 8. 7	272. 0 8. 8	265. 6 8. 9	284. 4 9. 2		296. 4 9. 9				3, 395. 9 9. 3
W. New York and W. Pennsylvania West Virginia Ohio Illinois Kentucky Michigan Kansas Oklahoma	1.8 9.6 .9 10.9 1.2 7.6 37.9	1. 7 8. 7 .8 10. 2 1. 1 .1 7. 1 35. 1	1. 7 8. 2 . 7 11. 3 . 8 . 2 7. 2 38. 0	1. 5 8. 6 . 6 11. 1 2. 8 . 2 6. 0 34. 6	2.7	.8 6.6 .3 11.1 2.6 .2 5.3 36.5	11.6 2.5 .3 5.6	.8 7.1 .3 11.4 2.7 .2 5.9 37.8	1.0 7.2 .4 11.9 2.8 .2 6.5 38.0	3. 2 3. 2 6. 8	3.3 .1 7.3	1. 7 10. 3 . 5 13. 3 3. 8 . 1 7. 7 38. 5	15. 5 99. 0 6. 3 140. 2 29. 5 2. 3 79. 0 446. 4
Texas: Gulf East Texas Panhandle Rest of Texas	35. 4 26. 4 40. 3 45. 8	32. 8 24. 1 33. 9 41. 7	34. 8 22. 7 36. 4 43. 6	25. 9 16. 0 31. 7 40. 7	33.7	28. 1 24. 0 33. 8 38. 8	29. 3 23. 8 35. 3 40. 2	31. 4 29. 9 32. 6 39. 4	32. 3 28. 2 33. 7 38. 0	28. 4 34. 5	37.1	34. 8 26. 0 40. 6 38. 5	381. 6 298. 7 423. 6 482. 9
Total Texas	147. 9 2. 9	132. 5 2. 7	137. 5 3. 5	114. 3 3. 3	126. 9 3. 6	124. 7 3. 6	128.6 3.7	133. 3 3. 7	132. 2 3. 7	135. 1 3. 9	133. 9 3. 7	139. 9 3. 6	1, 586. 8 41. 9
Louisiana: Gulf Inland	5. 5 22. 2	4. 9 19. 6	5. 5 18. 6	5. 2 14. 1	6. 0 17. 3	5. 1 18. 7	5. 9 18. 8	6. 1 19. 6	6. 3 19. 5	6. 6 20. 1	6. 2 20. 0	7. 1 20. 8	70. 4 229. 3
Total Louisiana New Mexico	27. 7 7. 1 . 5	24. 5 6. 6 . 4	24.1 7.4 .4	19.3 6.7 .4		23. 8 6. 8 . 4	24.7 7.6 .3	25. 7 8. 0 . 3	25. 8 7. 5 . 3	7.5 .3	26. 2 7. 3 . 4	27. 9 7. 4 . 5	299. 7 86. 7 4. 5
ming California	3. 2 55. 1	2.7 50.1	3. 1 50. 7	2.8 50.6	2. 9 52. 1	2. 7 50. 0	3.0 53.4	3.1 54.9	3.0 53.4	3.3 55.0	3, 4 53, 0	3. 4 57. 1	36, 6 635, 4
													3, 509. 8

<sup>1</sup> Subject to revision.

The output of liquefied petroleum gases at natural-gasoline plants in California rose from 82,638,000 gallons in 1941 to 89,973,000 gallons

in 1942, a modest gain for this branch of the industry.

Louisiana.—The production of the three light products in Louisiana increased 33 percent in 1942 over 1941. This increase was confined to cycle products (up 87 percent) and liquefied petroleum gases (up 110 percent), as the output of natural gasoline declined 22 percent. Much of the gain was due to the full year's operation of the large cycle plant in the Cotton Valley field.

Oklahoma.—Production in Oklahoma followed the usual trend, that is, with natural gasoline decreasing and liquefied petroleum gases In this case, however, the gain in gases was less than the loss in natural gasoline; hence the total declined 2 percent.

are no real cycle plants in the State.

Texas.—Production in Texas followed the same trend as in Louisiana, with increases for cycle products, liquefied petroleum gases, and the total but with a decline for natural gasoline. The total set a new record of 1,586,772,000 gallons, or 2 percent more than in 1941. output of cycle products increased 28 percent and liquefied petroleum gases 5 percent, but natural gasoline declined 13 percent.

Natural gasoline and allied products produced and natural gas treated in the United States in 1941, by States 1

		Natural g	gasoline	Cycle p	roducts	Liquef troleur		Natur	al gas tres	ated
State	Num- ber of						•		Average (gallons cu. f	per M
•	oper- ators 2	Thou- sands of gallons	Thou- sands of dollars	Thou- sands of gallons		Thou- sands of gallons	Thou- sands of dollars	Millions of cu. ft.	Natural gasoline (includ- ing cycle prod- ucts)	All light prod- ucts
Arkansas California Colorado Illinois Kansas Kentucky Louisiana Michigan	6 35 2 23 9 5 16 2	28, 108 577, 127 390 54, 872 72, 876 10, 247 117, 180 5, 670	24, 067 18 2, 693 2, 631 475 4, 025 261		2, 351		1, 054 410 1, 055 388	134 23, 732 176, 088 38, 062 191, 194 3, 581	1. 55 2. 91 2. 31 . 41 . 27 1. 05 1. 58	1.58
Montana New Mexico New York Ohio Oklahoma Pennsylvania Texas Utah West Virginia	1 6 1 8 47 55 101	2, 517 69, 115 17 8, 217 362, 247 15, 440 783, 736 808 65, 873	2, 049 1 401 16, 084 705 29, 479 45		14, 587	1, 449 11, 885  91, 136 571 378, 598  32, 171	2, 076 42	43, 704 1, 325, 471	. 66 3. 40 . 22 1. 81 . 35 . 89	.38 .77 3.40 .22 2.26 .37 1.18
Wyoming Total: 1941 1940	284	33, 920	1, 876 88, 877	480, 354	16, 938 (³)	1, 560	62		.97	1.65

4 Figures not available.

<sup>&</sup>lt;sup>1</sup> Complete figures for 1942 not yet available.

<sup>2</sup> A producer operating in more than one State is counted but once in arriving at total for United States.

<sup>3</sup> Cycle products included under natural gasoline.

The record of production by the major districts in Texas in 1942 shows the Gulf rapidly forging to the front but East Texas and the Panhandle losing ground, primarily because no cycle plants and little additional fractionating equipment were built outside of the Gulf district and adjoining counties in 1941 and 1942. As a matter of fact, the East Texas field did an outstanding job in holding its 1942

decline to less than 1 percent.

Other States.—Although the majority of this group declined in output in 1942, the total for all increased 9 percent, or from 498,219,000 gallons in 1941 to 541,485,000 gallons in 1942. This gain roughly equaled the rise in output of Illinois, where increased production, particularly of liquefied petroleum gases, continues to expand even though the gross gas output is declining. New Mexico and West Virginia continued to gain, but Kansas showed an unexpected decline.

#### CONSUMPTION AND MOVEMENTS

The total demand for all light products except liquefied refinery gases increased from 3,455,928,000 gallons in 1941 to 3,501,624,000 gallons in 1942—a rise of 1 to 2 percent. The gain was divided between cycle products and liquefied petroleum gases, as natural

gasoline alone declined about 10 percent.

The figures in the distribution table of this chapter indicate a material increase in the refinery utilization of natural gasoline and allied products in 1942; actually, however, there may have been a decline, because the production figures for 1941 were revised upward to include 707,196,000 gallons of liquefied petroleum gas, but the totals for refinery utilization were left unchanged. This threw most of the liquefied petroleum gases in 1941 into "sales to jobbers and retailers." This item consequently declined radically in 1942, when most of the gas was included in the proper category, "used at refineries."

Losses and exports rose from 345,618,000 gallons in 1941 to 392,-616,000 gallons in 1942. Although these two figures are not exactly comparable, probably there was an actual increase in this item.

Percentage of natural gasoline and allied products in refinery gasoline in the United States, 1938–42, by districts

Year	East Coast	Appa- lachian	Indiana, Illinois, Kentucky	Okla- homa, Kansas, Mis- souri	Texas Inland	Texas Gulf Coast	Louisi- ana Gulf Coast	Arkan- sas and Louisi- ana Inland	Rocky Moun- tain	Cali- fornia	Total
1938 1939 1940 1941 1942 1 2	1. 6 2. 7 2. 0 2. 3 1. 4	1. 4 1. 4 1. 6 1. 9 2. 1	4. 7 4. 1 4. 5 5. 3 5. 8	8. 8 7. 8 8. 0 6. 6 6. 3	15. 5 14. 3 16. 6 17. 6 16. 0	4. 3 3. 5 4. 4 5. 6 13. 9	2. 2 2. 1 1. 7 3. 7 15. 4	6. 8 5. 0 3. 3 6. 1 11. 6	5.8 4.7 4.5 4.4 4.8	17. 6 18. 0 15. 7 16. 1 16. 7	7. 2 6. 6 6. 6 7. 1 9. 7

Subject to revision.
 Not comparable with prior years because relatively more liquefied petroleum gas is included.

Distribution of natural gasoline and allied products in the United States, 1941-42, by months, in thousands of gallons

	January	Febru- ary	March	April	Мау	June	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total
Production	263, 634 8, 988	245, 406 7, 518	262, 878	261, 450	271, 950	265, 608	284, 424	292, 572 8, 652	296, 394 30, 996	312, 984 21, 126	315, 042 13, 146	323, 568 11, 844	3, 395, 910 60, 018
	272, 622	252, 924	262, 878	261, 450	271, 950	265, 608	284, 424	301, 224	327, 390	334, 110	328, 188	335, 412	3, 455, 928
Used at refineries <sup>1</sup> Sales:	160, 776	139, 104	158, 508	146, 916	142, 758	147, 756	152, 376	173, 460	199, 542	209, 874	189, 756	187, 824	2, 008, 650
To jobbers and retailers Liquefied petroleum gases for fuel Increase in all stocks	72, 198 23, 016	64, 134 20, 790	67, 158 22, 176 840	58, 338 21, 756 7, 266	62, 286 20, 076 14, 784	58, 380 22, 092 15, 918	69, 384 22, 386 3, 444	68, 418 20, 118	69, 132 20, 622	75, 726 21, 546	80, 472 23, 520	92, 232 25, 704	837, 858 263, 802
Losses and exports	16, 632	28, 896	14, 196	27, 174	32, 046	21, 462	36, 834	39, 228	38, 094	26, 964	34, 440	29, 652	345, 618
	272, 622	252, 924	262, 878	261, 450	271, 950	265, 608	284, 424	301,224	327, 390	334, 110	328, 188	335, 412	3, 455, 928
Production: Natural gasoline Cycle products Liquefied petroleum gases Liquefied refinery gases Decrease in all stocks	179, 928 61, 362 73, 206 9, 954	168, 840 54, 684 60, 732 10, 248	173, 082 59, 346 62, 412 9, 660	161, 490 47, 754 53, 550 12, 768	170, 436 53, 760 57, 960 21, 798	162, 792 52, 206 60, 438 21, 042 3, 570	170, 478 54, 600 60, 690 20, 622	173, 082 56, 028 66, 066 18, 606 7, 518	173, 250 54, 978 65, 688 17, 010 13, 860	171, 276 57, 078 76, 398 13, 272 27, 762	167, 790 55, 902 76, 860 17, 094 17, 262	170, 058 57, 834 87, 780 20, 160 14, 574	2, 042, 502 665, 532 801, 780 192, 234
	324, 450	294, 504	304, 500	275, 562	303, 954	300, 048	306, 390	321, 300	324, 786	345, 786	334, 908	350, 406	3, 702, 048
Used at refineries <sup>1</sup>	224, 742	187, 152	185, 388	169, 932	179, 424	185, 766	192, 234	206, 178	214, 536	229, 110	209, 538	207, 018	2, 391, 018
densate to jobbers and retail outlets Sales for fuel purposes:	14, 910	32, 382	42, 882	37, 548	37, 842	38, 724	35, 322	37, 716	33, 138	31, 164	36, 540	37, 632	415, 800
Liquefied petroleum gases Liquefied refinery gases Liquefied refinery gases Losses and exports Losses and ex	29, 820 9, 954 15, 330	24, 234 9, 324 18, 018	23, 352 10, 038 16, 884	24, 024 11, 340 19, 194	20, 286 19, 152 24, 696	20, 916 22, 470	22, 512 21, 420 2, 184	21, 084 18, 438	24, 318 16, 212	27, 846 14, 490	28, 854 16, 380	34, 944 19, 446	302, 190 188, 664 11, 760
Losses and exports	29, 694 324, 450	23, 394	25, 956 304, 500	13, 524 275, 562	22, 554 303, 954	32, 172	32, 718 306, 390	37, 884	36, 582 324, 786	43, 176 345, 786	43, 596 334, 908	51, 366 350, 406	392, 616 3, 702, 048

Includes quantities run through pipe lines.
 Subject to revision.

# Natural gasoline and allied products utilized at refineries in the United States, 1941-42, by districts and months, in thousands of gallons

District	January	Febru- ary	March	April	May	June	July	August	Septem- ber	October	Novem- ber	Decem- ber	Total
East Coast	8, 778	7, 518	6, 258	5, 376	5, 418	4, 368	5, 670	6, 090	7, 770	7, 770	8, 568	9, 744	83, 328
	1, 428	1, 722	1, 764	2, 142	1, 554	1, 218	1, 596	1, 134	1, 974	1, 848	1, 806	2, 106	20, 286
	24, 780	22, 680	22, 890	24, 864	23, 184	23, 226	25, 158	26, 208	28, 224	30, 618	28, 350	29, 400	309, 582
	17, 976	14, 784	15, 792	14, 070	13, 734	12, 936	14, 154	15, 960	20, 118	18, 606	20, 034	19, 236	197, 400
Texas: Gulf Coast Inland	21, 924	19, 152	25, 662	27, 174	25, 074	29,610	28, 812	35, 868	46, 536	43, 932	42, 000	46, 914	392, 658
	32, 004	24, 990	26, 964	23, 058	24, 234	24,990	24, 864	28, 056	28, 728	32, 550	27, 090	29, 316	326, 844
Total Texas	53, 928	44, 142	52, 626	50, 232	49, 308	54,600	53, 676	63, 924	75, 264	76, 482	69, 090	76, 230	719, 502
Louisiana-Arkansas:  Louisiana Gulf Coast	1, 050	798	1, 428	1,008	1, 344	924	924	3, 906	4, 284	5, 376	5, 502	6, 174	32, 718
	2, 226	1,890	1, 470	1,386	1, 134	1, 260	1, 386	4, 578	4, 662	5, 880	3, 696	4, 158	33, 726
Total Louisiana-Arkansas	3, 276	2, 688	2, 898	2, 394	2, 478	2, 184	2, 310	8, 484	8, 946	11, 256	9, 198	10, 332	66, 444
	3, 780	3, 108	2, 646	2, 184	2, 352	2, 100	1, 638	2, 352	2, 310	3, 150	3, 822	3, 696	33, 138
	46, 830	42, 462	53, 634	45, 654	44, 730	47, 124	48, 174	49, 308	54, 936	60, 144	48, 888	37, 086	578, 970
Total United States	160, 776	139, 104	158, 508	146, 916	142, 758	147, 756	152, 376	173, 460	199, 542	209, 874	189, 756	187, 824	2,008,650
East Coast	7, 476	5, 502	3, 360	2, 772	1, 134	2, 100	2,856	3, 318	2, 856	1, 764	2, 226	1, 218	36, 582
	2, 352	1, 764	1, 722	1, 596	1, 554	1, 596	2,100	1, 344	1, 512	1, 974	2, 268	1, 680	21, 462
	24, 276	22, 302	22, 344	20, 118	23, 142	26, 754	27,972	31, 248	33, 264	32, 340	27, 804	27, 006	318, 570
	15, 834	15, 624	13, 818	12, 600	12, 306	12, 642	12,096	12, 852	14, 952	16, 338	17, 598	15, 372	172, 032
Texas: Gulf Coast Inland	83, 538	54, 810	53, 298	54, 558	56, 910	58, 422	56, 826	67, 074	65, 688	66, 822	63, 546	66, 066	747, 558
	29, 022	29, 232	21, 462	16, 296	19, 824	18, 984	20, 706	21, 336	21, 882	25, 536	22, 806	18, 018	265, 104
Total Texas	112, 560	84, 042	74, 760	70, 854	76, 734	77, 406	77, 532	88, 410	87, 570	92, 358	86, 352	84, 084	1, 012, 662
Louisiana-Arkansas: Louisiana Gulf CoastArkansas and Louisiana Inland	8, 274	8, 610	16, 002	12, 180	9, 996	11, 760	11, 214	8, 148	10, 668	16, 086	13, 440	14, 700	141, 078
	4, 956	3, 150	2, 730	2, 814	4, 116	4, 158	6, 636	6, 090	6, 762	6, 552	4, 956	4, 998	57, 918
Total Louisiana-Arkansas	13, 230	11, 760	18, 732	14, 994	14, 112	15, 918	17, 850	14, 238	17, 430	22, 638	18, 396	19, 698	198, 996
	3, 948	3, 066	2, 688	1, 764	1, 092	1, 302	1, 680	2, 016	2, 268	4, 200	4, 788	4, 662	33, 474
	45, 066	43, 092	47, 964	45, 234	49, 350	48, 048	50, 148	52, 752	54, 684	57, 498	50, 106	53, 298	597, 240
Total United States	224, 742	187, 152	185, 388	169, 932	179, 424	185, 766	192, 234	206, 178	214, 536	229, 110	209, 538	207, 018	2, 391, 018

<sup>1</sup> Subject to revision.

Refinery utilization.—The proportion of natural gasoline used at refineries increased from 7.1 percent in 1941 to 9.7 percent in 1942, but here also is a lack of comparability. The figures for most of the districts are comparable; for example, the decline indicated for the East coast and the gain in California undoubtedly occurred.

Direct sales.—Comparable data on "direct sales," or sales to other than refiners, are lacking in 1942. This type of distribution would be expected to increase, as much of the cycle production never reaches a

refinery.

#### STOCKS

Stocks of natural-gasoline and cycle products continued to decline in 1942, although the net change was much less than in 1941. The total, as of December 31, 1942, was 170,898,000 gallons compared with 179,550,000 gallons the first of the year. The decrease of about 9,000,000 gallons comprised a decline of about 14,000,000 gallons in natural gasoline and an increase of about 5,000,000 gallons in cycle products. Stocks of liquefied petroleum gases nearly quadrupled during the year; stocks of liquefied refining gases at refineries increased. Including the two kinds of liquefied gases (petroleum and refinery), stocks increased from 191,730,000 gallons on January 1 to 203,490,000 gallons on December 31.

The downward trend in natural-gasoline stocks in California in 1941 carried over into 1942. As the decline in California exceeded the national total, stocks of natural gasoline east of California increased. Quantitatively most of the increase east of California was at plants in Texas, although several other States had larger relative gains.

Stocks of natural gasoline and allied products in the United States in 1942, by months, in thousands of gallons

Date	Natural	Cycle	Liquefie	ed gases	Total		
2000	gasoline	products	Petroleum	Refinery	Total		
January 1.  January 31.  February 28.  March 31.  April 30.  May 31.  June 30.  July 31.  August 31.  September 30.  October 31.  November 30.  December 31.	171, 276 179, 676 193, 368 206, 892 228, 060 245, 868 244, 608 246, 372 235, 242 216, 930 192, 486 173, 376 157, 374	8, 274 9, 408 13, 062 14, 826 13, 020 16, 128 12, 474 14, 868 13, 692 14, 826 15, 036 12, 390 13, 524	6, 804 12, 600 12, 348 14, 322 12, 726 13, 860 16, 632 15, 456 20, 076 22, 596 24, 066 23, 646	5, 376 5, 376 6, 300 5, 922 7, 350 9, 996 8, 568 8, 7, 770 7, 938 8, 736 7, 518 8, 232 8, 946	191, 730 207, 060 225, 078 241, 962 261, 156 285, 852 282, 282 284, 466 276, 948 263, 088 225, 326 218, 064 203, 490		

#### TECHNOLOGIC DEVELOPMENTS

Cycling plants.—The equipment shortage brought on by the war prevented much expansion of the cycling branch of the industry, but some plants on which construction was started in 1941 were completed and put in operation in 1942. Thus 37 plants were reported as operating in 1942 compared with 30 in 1941 and 24 in 1940. These figures include only bonafide cycling plants and not natural-gasoline plants that repressure.

Cycling plants in Texas processed 425,000,000,000 cubic feet of gas in 1942 and obtained an average yield of 0.92 gallon of liquid per

The plants in Louisiana processed about thousand cubic feet.

42,000,000,000 cubic feet, with a considerably higher yield.

Yields.—The average yield for natural gasoline and cycle products in 1941 was 0.97 gallon per thousand—a slight increase over the 0.95 gallon for 1940. This gain may be attributed principally to an increase in Texas from 0.83 gallon in 1940 to 0.89 gallon in 1941 and in Illinois from 1.69 to 2.31. The gain in yields in Illinois in 1940 and 1941 is typical of the performance of a group of fields that have experienced too rapid withdrawal of crude oil. In nearly all such fields the output of casinghead gas declines rapidly, but its gasoline content increases.

Natural gasoline and allied products produced in the United States in 1941, by States and by methods of manufacture 1

	Nu	mber of pl	ants operat	ing	Product	ion (thousa	nds of ga	llons)
State	Compression 2	Absorp-	Charcoal	Cycling 5	Compression ?	Absorp- tion 3/4	Char- coal	Cy- cling \$
Arkansas. California California Colorado. Illinois Kansas. Kentucky Louisiana Michigan Montana. New Mexico. New York Ohio Oklahoma. Pennsylvania Texas. Utah	2 1 43 2 3 3 1 1 3 32 68 31	9 89 1 5 12 25 2 27 7 7 8 81 11	1 1	1	2, 225 124 1, 711 1, 626 1, 166 2, 913 1, 503 	34, 389 657, 540 91, 454 84, 065 •34, 020 134, 356 4, 167 3, 966 81, 000 6, 867 411, 681 13, 948 1, 004, 381	1,321	88, 455
West Virginia Wyoming	50	22 4	3		24, 269 23, 920	70, 436 11, 560	3, 339	
Total: 1941	243 245	397 407	6 8	30 24	255, 150 7 166, 482	2, 644, 824 72, 002, 385	4, 872 4, 843	491, 06 7165, 69

Figures for 1942 not yet available.
 Includes 22 plants manufacturing liquefied petroleum gases.
 Includes combination of absorption process with compression and charcoal processes.
 Includes 159 plants manufacturing liquefied petroleum gases.
 Includes 8 plants manufacturing liquefied petroleum gases.
 Includes 8 plants manufacturing liquefied petroleum gases.
 To Drip gasoline.
 Does not include liquefied petroleum gases.

Production by processes.—In previous years cycle plants were classed as compression plants; in consequence, that group increased in relative importance during 1939 and 1940. However, in this year's table on "methods of manufacture" the number of cycle plants and the production are shown separately, by States. The data for 1941 (1942) figures for other than cycle plants are not yet available) indicate that the three old classes (compression, absorption, and charcoal) all declined in number of plants compared with 1940. Compression production probably declined throughout 1942, absorption production probably declined in 1942 after a gain in 1941, and the small output of charcoal plants probably declined in 1942.

Trends in vapor pressures.—During the year the Bureau's monthly questionnaire on natural gasoline was revised, and the queries on vapor pressure of shipments were replaced by items covering a breakdown of production by vapor pressures. Data on the new basis for east of California for 1942 show an average vapor pressure of 20.5 pounds. This compares with an average of 19.7 pounds for total

shipments east of California in 1941.

Technical trends.—Because of the shortage of materials, little in the way of new equipment and methods was introduced in the natural-gasoline industry in 1942. The primary consideration continued to be the maximum use of isobutane, isopentane, and other fractions in the aviation-gasoline program. It has been reported that participation of the industry in aviation-gasoline production will approach 70,000 barrels daily by the end of 1943. The extent to which the rubber and other war programs depend on natural gasoline and allied products for raw materials is probably increasing, but relatively the quantities involved are small.

## LIQUEFIED PETROLEUM GASES

Sales of liquefied petroleum gases continued to expand strongly in 1942, as in recent years; however, difficulties connected with the war probably prevented full supplying of the potential market. Distributors of liquefied petroleum gases reported sales of 585,440,000 gallons in 1942—a 27-percent gain over 1941 deliveries of 462,852,000 gallons. The increase in 1942 compares with a 48-percent growth in demand in 1941 and a 40-percent gain in 1940, and it is surprising that dealers troubled by the shifting of supplies to raw material uses, inadequate transportation, lack of sufficient equipment, and other handicaps made the showing reported. The fact that the general public is rapidly learning to appreciate the many advantages and diversified uses of liquefied petroleum gases is evident in the rapidly growing market demand, which has approximately doubled since 1940.

Sales of liquefied petroleum gases in the United States, 1936-42, in thousands of gallons

				1	To	otal
Year	Butane	Propane	Butane- propane mixtures	Pentane	Quantity	Percent of increase over preceding year
1936	40, 200 45, 399 52, 768 71, 351 77, 056 112, 244 128, 560	36, 502 46, 474 54, 130 79, 323 109, 216 126, 969 150, 511	27, 375 46, 694 56, 050 69, 020 123, 348 219, 252 301, 917	2, 575 2, 833 2, 253 3, 886 3, 836 4, 387 4, 452	106, 652 141, 400 165, 201 223, 580 313, 456 462, 852 585, 440	38. 8 32. 6 16. 8 35. 3 40. 2 47. 7 26. 5

<sup>&</sup>lt;sup>1</sup> Subject to revision.

All principal uses of liquefied petroleum gases made important gains in 1942 over 1941. The quantity (299,559,000 gallons) reported for domestic or household consumption in 1942 was 36 percent above the 1941 total (220,722,000 gallons)—a percentage increase somewhat below those made in 1941 (65 percent) and 1940 (53 percent); however, it must be realized that normal distribution to increasing numbers of consumers was impossible under conditions prevailing in 1942. Gasmanufacturing companies purchased 24 percent more liquefied petroleum gases in 1942 (31,366,000 gallons) than in 1941 (25,255,000 gal-

lons), about the same gain in requirements as was made in 1941 over 1940. A 41-percent expansion in the sales of liquefied petroleum gases for industrial fuel reported in 1941 (98,728,000 gallons) was not reached in 1942 (114,132,000 gallons), as the increase over 1941 was only 16 percent. Difficulty in obtaining the more desirable butane for use as an industrial fuel was probably one of the reasons for the smaller relative growth in this particular use in 1942. Manufacturers of chemicals required 53,038,000 gallons of liquefied petroleum gases in 1942 or 20 percent more than the 1941 total of 44,206,000 gallons—a gain compared with a 28-percent increase in 1941 over 1940. Deliveries of 82,456,000 gallons of liquefied petroleum gases for internal-combustion-engine fuel in 1942 were 23 percent above the 1941 total of 66,871,000 gallons or about the same increment (24 percent) as reported in 1941.

About one-fifth (22 percent) of total liquefied petroleum gas sales in 1942 was reported as butane compared with one-fourth (24 percent) in 1941 deliveries. This drop in the butane proportion in the 1942 total followed a downward trend of recent years and a change that probably will continue as more butane is diverted for the manufacture of motor fuel, rubber, and other products. The propane share in the marketed production of liquefied petroleum gases also continued to decrease (27 percent in 1941 and 26 percent in 1942), while the proportion of butane-propane mixtures in total deliveries accounted for a larger percentage. Butane-propane mixtures replacing butane for many uses constituted about 52 percent of total sales of liquified petroleum gases in 1942 compared with a 47-percent share in 1941. Pentane, which is relatively unimportant in volume, made up less than

1 percent of total requirements both in 1941 and 1942.

Sales of butane increased from 112,244,000 gallons in 1941 to 128,560,000 gallons in 1942—a 15-percent gain. The rate of increase in 1942 was well below the 46-percent expansion for butane deliveries in 1941. The gains for the principal uses of butane were smaller than those reported for 1941, except for the chemical-manufacturing industry, which purchased 5,256,000 gallons of butane in 1942 compared with negligible amounts in previous years. Butane as well as propane is evidently replacing butane-propane mixtures as raw material at chemical plants, as "mixtures" showed a small decline in 1942. Butane delivered for internal-combustion-engine fuel, which increased 67 percent in 1941 over 1940, dropped from 18,799,000 gallons in 1941 to 14,870,000 in 1942, a loss of 21 percent, evidently because of the diversion of butane to war industries.

The marketed production of propane was reported as 150,511,000 gallons in 1942 compared with 126,969,000 gallons in 1941, an increase of 19 percent and a rate slightly above the 16-percent gain realized in 1941. The quantity of propane delivered for domestic use—113,249,000 gallons in 1942—was 16 percent (42-percent gain in 1941 over 1940) above the 1941 total of 98,048,000 gallons. The much lower rate of expansion in 1942 reflects the inability of distributors to fully supply the potential domestic market under disturbed conditions prevailing during the year. Gas-manufacturing companies bought 26 percent less propane (4,957,000 gallons in 1942 and 6,678,000 in 1941) in 1942 but increased their purchases of butane (by 2 percent over 1941) and butane-propane mixtures (119 percent over 1941).

Propane delivered to manufacturing plants rose by 23 percent, from 16,730,000 gallons in 1941 to 20,601,000 in 1942. Industrialists turned to propane for fuel and other uses in 1942 as more of the butane supply was diverted to other channels. This is a change from 1941, when less propane (by 50 percent) was used by manufacturers than in 1940. The requirements for propane by chemical plants increased from 1,528,000 gallons in 1941 to 5,850,000 in 1942, paralleling a similar gain in butane sales to manufacturing chemical firms. The quantity of propane reported as internal-combustion-engine fuel nearly doubled in 1942 (3,112,000 gallons in 1942 compared with 1,631,000 in 1941), replacing butane used as motor fuel, which showed

a drop in 1942.

The marketed production of butane-propane mixtures rose from 219,252,000 gallons in 1941 to 301,917,000 gallons in 1942. percent gain for 1942 was far below the 78 percent expansion in deliveries reported for 1941; however, the percentage increase for butanepropane mixtures in 1942 was still well above the rates reported for the other liquefied gases, as it was in 1941. All principal demands for butane-propane mixtures showed substantial gains in 1942 over 1941, except for a minor decline (2 percent below 1941) in the quantity The domestic use of butanecredited to chemical manufacturers. propane mixtures increased from 87,673,000 gallons in 1941 to 140,-516,000 in 1942 or by 60 percent compared with over a 100-percent gain in 1941. Incidentally, the quantity of butane-propane mixtures reported for domestic use in 1942 exceeded for the first time the propane delivered for the same purpose. Sales of butane-propane mixtures to gas-manufacturing companies more than doubled in 1942 (13,-961,000 gallons in 1942 compared with 6,368,000 in 1941) contrasted with a minor increase (2 percent over 1941) in butane requirements and a sharp decline (26 percent below 1941) in purchases of propane. The quantity of butane-propane mixtures used as industrial fuel in 1942—43,011,000 gallons—was 22 percent above the 1941 total— 35,287,000 gallons. Butane-propane mixtures are important as raw material for the manufacture of chemicals; however, requirements dropped slightly from 39,243,000 gallons in 1941 to 38,325,000 in 1942, in contrast with larger purchases of butane and propane by chemical The demand for butane-propane mixtures for motor fuel-64,470,000 gallons in 1942—was 39 percent above 1941 requirements— 46,441,000 gallons. The indications are that butane (21-percent decrease in 1942) for this purpose is being replaced mostly by butanepropane mixtures and less extensively by propane.

Deliveries of pentane increased slightly from 4,387,000 gallons in 1941 to 4,452,000 in 1942. The larger share of this gas is used in the manufacture of chemicals, the quantity increasing from 3,146,000 gallons in 1941 to 3,607,000 in 1942. The sales of pentane for domestic consumption, which rose from 656,000 gallons in 1940 to 1,128,000 in

1941, declined to 766,000 in 1942.

The changing proportions of the various liquefied gases sold to satisfy the principal uses are of special interest. Butane delivered for domestic consumption has remained at about 15 percent of total requirements in recent years, whereas the proportion of propane so used has declined from about 51 percent in 1940 to 38 percent in 1942, and the butane-propane mixtures have gained in about the reversed ratio. Liquefied petroleum gases sold to gas-manufacturing companies in

1940 were over half butane and about a quarter propane; but in 1942 butane-propane mixtures represented the larger share (45 percent), with corresponding losses in the butane and propane percentage totals.

Sales of liquefied petroleum gases in the United States, 1941-42, by uses, methods of transportation, and regional distribution, in thousands of gallons

	D	<b>D</b>	Butane-		То	tal
	Butane	Propane	propane mixtures	Pentane	Quantity	Percent
1941 By uses:	•					
Domostio	33, 873	98, 048	87, 673	1, 128	220, 722	47.7
Gas manufacturing	12, 152	6, 678	6, 368	57	25, 255	5.
Industrial mei	46, 677 289	16, 730	35, 287	34	98, 728	21. 3
Chemical manufacturing Internal-combustion-engine fuel	18, 799	1, 528 1, 631	39, 243 46, 441	3, 146	44, 206 66, 871	9. ( 14. 4
All other uses	454	2, 354	4, 240	22	7,070	1.
Percent of total	112, 244 24, 3	126, 969 27, 4	219, 252 47, 4	4, 387 0. 9	462, 852 100. 0	100. (
By methods of transportation:						
Bulk 1	111,896	73, 511	216, 320	4, 171	405, 898	87. 7
Bulk <sup>1</sup> Cylinders <sup>1</sup>	348	53, 458	2, 932	216	56, 954	12. 8
	112, 244	126, 969	219, 252	4, 387	462, 852	100. (
Regional distribution:	00.000	14.000	40.051		100.00	
Pacific Coast area All other areas	26, 628 85, 616	14, 006 112, 963	62, 251 157, 001	4, 387	102, 885 359, 967	22. 2 77. 8
	112, 244	126, 969	219, 252	4, 387	462, 852	100. (
1942 ²		e de la composição				. 1
By uses:	45 000	110 010	***		000 550	
Domestic Gas manufacturing	45, 028 12, 419	113, 249 4, 957	140, 516 13, 961	766 29	299, 559 31, 366	51. 2 5. 3
Industrial fuel	50, 495	20, 601	43, 011	25	114, 132	19.
Chemical manufacturing	5, 256	5, 850	38, 325	3, 607	53, 038	9.
Internal-combustion-engine fuel	14,870	3, 112	64, 470	4	82, 456	14.
All other uses	492	2,742	1,634	21	4,889	
Percent of total	128, 560 21. 9	150, 511 25. 7	301, 917 51. 6	4, 452 0. 8	585, 440 100. 0	100. (
By methods of transportation:						
Bulk	127, 492	88, 340	297, 511	4, 161	517, 504	88. 4
Cylinders and drums	1,068	62, 171	4, 406	291	67, 936	11. 6
	128, 560	150, 511	301, 917	4, 452	585, 440	100. (
Regional distribution:	10.04	15.000	00.050		100 002	
Pacific Coast areaAll other areas	10, 044 118, 516	17, 803 132, 708	99, 058 202, 859	4, 452	126, 905 458, 535	21. 7 78. 3
	128, 560	150, 511	301, 917	4, 452	585, 440	100. (

<sup>1</sup> Revised figures.
2 Subject to revision.

Industrial fuel was approximately 48 percent butane in 1940 and 1941, but the proportion dropped to 44 percent in 1942, as butane was diverted for raw material. Propane, which comprised 47 percent of the industrial fuel total in 1940, dropped to 17 percent in 1941 and 18 percent in 1942. Butane-propane mixtures rose from 5 percent of the industrial fuel total in 1940 to 36 percent in 1941 and 38 percent in 1942. "Mixtures" used for raw materials in the manufacture of chemicals constituting about 88 percent of the total demand in 1940 and 1941 declined to 72 percent in 1942, and the butane and propane proportions each rose to about 10 percent of the total. Pentane delivered to chemical manufacturers has declined from 9 percent of

total requirements in 1940 to 7 percent in 1942. Butane used for motor fuel increased from 21 percent of the total in 1940 to 28 percent in 1941 but then declined to 18 percent in 1942. Butane-propane mixtures made up 70 percent of the internal-combustion-engine fuel total in 1941 and 78 percent in 1942.

The American Gas Association has furnished the following data concerning the distribution of liquefied petroleum gas by manufac-

tured-gas companies in 1942:

At the end of 1942, liquefied petroleum gas was being delivered through mains to consumers in 208 communities in 31 States by 92 companies supplying 69,140

Butane-air gas with heating value ranging from 520 to 1,300 B. t. u. per cu. ft. was supplied to 153 communities in 30 States. A mixture of undiluted butane and propane gas with a heating value of 2,800 to 3,000 B. t. u. per cu. ft. was supplied to 15 communities in Arizona, California, and Nevada. Undiluted propane gas with a heating value of 2,550 B. t. u. per cu. ft. was supplied to 40 communities in Maryland, Minnesota, New Jersey, North Dakota, Virginia, and Wisconsin.

Bulk shipments of liquefied petroleum gases increased from 405,-898,000 gallons in 1941 to 517,504,000 in 1942, and quantities handled in cylinders were 56,954,000 gallons in 1941 and 67,936,000 in 1942. The trend toward bulk shipments of liquefied petroleum gases, which was rather pronounced in 1941, was also evident in 1942, and over 88 percent of total deliveries were handled in bulk, either in tank cars or trucks. Shortage of material for making containers and the greater ease of handling bulk shipments under present transportation conditions probably will force an even larger proportion of bulk deliveries in the future.

Deliveries of liquefied petroleum gases in the Pacific Coast area (California, Oregon, Washington, Arizona, and Nevada) increased from 102,885,000 gallons in 1941 to 126,905,000 in 1942, a gain of 23 percent. The demand for liquefied petroleum gases on the Pacific coast represented 22 percent of the national total in both 1941 and 1942. The marketed production of liquefied petroleum gases in all other areas expanded by 27 percent—from 359,967,000 gallons in

1941 to 458,535,000 in 1942.

## CARBON BLACK

By G. R. HOPKINS AND H. BACKUS

#### SUMMARY OUTLINE

	Page	r 🔭	Page
Summary	1177	Demand	1181
Salient statistics	1178	Total deliveries	. 1181
Historic data		Domestic consumption	1181
Production	1179	Exports and imports	
By States	1179	Stocks	. 1184
Methods and yields	1179	Prices and values.	. 1184
Number and capacity of plants	1180		
Duodencour	1190		

#### SUMMARY

A number of factors combined to bring about adverse conditions in the carbon-black industry during 1942. Anticipating a rise in price, which occurred in January, consumers replenished their supplies at the end of 1941. Reductions in exports because of the war, as well as in rubber manufacture, contributed to a decrease in demand that was not offset by increased sales for military purposes. Production declined 3 percent from the 1941 total, whereas sales declined 30 percent, resulting in a large accumulation of stocks held by producers at the end of the year. (See fig. 1.)

In spite of the decline in rubber manufacture in 1942, about 89 percent of domestic sales went to the rubber trade. Toward the end of the year demands from the synthetic-rubber industry were taking up part of the slack. All the major classes of consumption decreased




FIGURE 1.-Production, stocks, and deliveries of carbon black, 1919-42.

quantitatively, but their ratio to total demand remained virtually

unchanged.

The Office of Price Administration allowed a rise of 0.2 cent a pound for both compressed and uncompressed grades of carbon black the first week in January. Prices were unchanged during the remainder of the year.

Salient statistics of carbon black produced from natural gas in the United States, 1938–42

	1938	1939	1940	1941	1942
Number of producers reporting Number of plants	24 55	22 49	22 51	21 49	21 50
Quantity produced: By States and districts: Louisianapounds	39, 534, 000	51, 734, 000	55, 610, 000	78, 050, 000	90, 353, 000
Texas: Panhandle districtdo Rest of Statedo	382, 369, 000 34, 735, 000	410, 130, 000 43, 044, 000	423, 908, 000 55, 987, 000	415, 001, 000 65, 211, 000	380, 536, 000 54, 353, 000
Total Texas do do do do do do do do do do do do do	417, 104, 000 20, 401, 000	453, 174, 000 20, 258, 000	479, 895, 000 33, 287, 000	480, 212, 000 35, 803, 000	434, 889, 000 48, 764, 000
Total United Statesdo	477, 039, 000	525, 166, 000	568, 792, 600	594, 065, 000	574, 006, 000
By processes:  Contact processes 1 do Furnace processes 2 do	446, 241, 000 30, 798, 000	469, 150, 000 56, 016, 000	497, 026, 000 71, 766, 000	492, 857, 000 101, 208, 000	428, 665, 000 145, 341, 000
Stocks held by producers Dec. 31 poundsdodo	166, 159, 000 * 65, 000	130, 792, 000	169, 587, 000 223, 000	118, 847, 000 61, 000	242, 755, 000 167, 000
Quantity sold:  Domestic deliveries—  To rubber companiesdo  To ink companiesdo  To paint companiesdo  For miscellaneous purposes pounds	217, 231, 000 14, 131, 000 4, 229, 000 7, 883, 000	316, 621, 000 21, 929, 000 6, 382, 000 11, 773, 000	310, 179, 000 24, 159, 000 6, 806, 000 11, 012, 000	439, 502, 000 28, 198, 000 5, 840, 000 23, 039, 000	295, 947, 000 19, 233, 000 3, 616, 000 15, 500, 000
Total domestic deliveries pounds_ Exportdo	243, 474, 000 167, 968, 000	356, 705, 000 203, 828, 000	352, 156, 000 177, 618, 000	496, 579, 000 148, 165, 000	334, 296, 000 115, 635, 000
Total solddoValue (at plants) of carbon black produced:	411, 442, 000	560, 533, 000	529, 774, 000	644, 744, 000	449, 931, 000
A verage per pound cents	\$11, 486, 000 2. 41	\$12, 857, 000 2. 45	\$16, 510, 000 2. 90	\$19, 341, 000 3. 26	\$19, 547, 000 3. 41
Estimated quantity of natural gas used	324, 950, 000	347, 270, 000	368, 802, 000	365, 377, 000	335, 533, 000
M cubic feetpounds_ Average value of natural gas used	1. 47	1.51	1.54	1. 63	1.71
per M cubic feetcents.	.89	.94	1.00	1.13	1. 29

<sup>1</sup> Principally channel.
2 Includes furnace, thermatomic, and Lewis.
3 Gain.

Summary of statistics for carbon black produced from natural gas in the United States, 1919-42

Year Production (thousands of pounds) Value (thousands of dollars)			Stocks at end of year	Sales (tho	Average yield (pounds	
	(thousands of pounds)	Domestic	Export	per M cubic feet of gas)		
1919	52, 057	3, 816	(1)	(1)	(2) (2) (2)	1.04
1920		4, 032 5, 446	(2)			1. 26 1. 18
1921 1922	59, 766 67, 795	5, 820	2, 435		8	1. 26
1923	138, 263	11, 692	38, 321	2 102, 210	2	1. 27
1924	186, 872	11, 565	95, 671	2 128, 861	(2)	1. 19
1925	177, 417	9, 640	96, 023	132, 449	43, 183	1, 26
1926	180, 576	9, 939	108, 378	128, 294	39, 211	1, 39
1927	198, 429	10, 955	82, 831	168, 999	54, 431	1. 38
1928	248, 790	13, 782	50, 240	202, 676	77, 903	1.42
1929	366, 442	18, 720	132, 203	191, 977	91, 829	1.40
1930	379, 942	14, 852	259, 245	167, 279	84, 260	1.43
1931	280, 907	8, 621	280, 010 3 281, 667	161, 712	96, 714	1. 44
1932	242, 700	6,664	257, 998	161, 483	100, 072	1,44
1933	273, 125	7, 602	155, 969	222, 182	152, 286	1, 44
1934	328, 828	11, 654	171, 799	191, 992	120, 620	1, 43
1935	352, 749	13, 755	136, 086	245, 351	142, 185	1. 46
1936	411, 345	16, 110	79, 582	313, 018	154, 718	1. 45
1937	510, 606	17, 389	100, <b>497</b> 166, 159	305, 362 243, 474	184, 253 167, 968	1, 50 1, 47
1938	477, 039 525, 166	11, 486 12, 857	130, 792	356, 705	203, 828	1. 51
939	568, 792	16, 510	169, 587	352, 156	177, 618	1. 54
940	594, 065	19, 341	118, 847	496, 579	148, 165	1. 63
1941	,574, 006	19, 547	242, 755	334, 296	115, 635	1.71

1 Figures not available.

2 Exports not separately reported by the Department of Commerce before 1925. For comparison with 1932.

#### PRODUCTION

By States.—Texas produced 76 percent of the United States total output in 1942 compared with 81 percent in 1941 and 84 percent in 1940. Its output was 434,889,000 pounds, a 9-percent decline from the 1941 record. Although the Panhandle district produced 8 percent less carbon black than in 1941, it contributed 87.5 percent of the State total in 1942 compared with 86.4 percent in 1941.

Louisiana gained 16 percent over 1941, owing principally to increased output of furnace blacks. Production was 90,353,000 pounds

in 1942 compared with 78,050,000 pounds in 1941.

Oklahoma and Kansas both had less production than in 1941. New Mexico and California were added to the list of producing States

during the year.

Methods and yields.—Because of the growing importance of furnace blacks, it has been decided to divide the figures according to contact processes and furnace or retort processes instead of channel and "Other processes" as has been done in former years.

Carbon black produced from natural gas in the United States in 1942, by States and by major producing districts

	ng 1		I	roduction	N	Natural gas used			
State and district	eporti	plants		Value at	plant		d per feet	Valu	1e
State and district	Producers reporting	Number of	Pounds	Total	Average (cents)	M cubic feet	Average yield per M cubic feet (pounds)	Total	Average per M cubic feet (cents)
California Kansas New Mexico Louisiana: Monroe- Richland district (Morehouse and	1 2 1	1 2 1	24, 446, 000	\$512,000	2. 09	8, 225, 000	2.97	\$368, 000	4. 47
Ouachita Parishes) Oklahoma	6 4	6 4	90, 353, 000 24, 318, 000	3, 258, 000 809, 000	3. 61 3. 33	18, 040, 000 9, 789, 000	5. 01 2. 48	504, 000 163, 000	2.79 1.67
Texas: Panhandle district (Carson, Gray, Hutchinson, Moore, and Wheeler Coun-									
ties) Rest of State (Aransas, Nueces, Stephens, Ward, and Winkler	16	29	380, 536, 000	13, 152, 000	3. 46	269, 136, 000	1.41	3, 073, 000	1.14
Counties)	5	7	54, 353, 000	1, 816, 000	3,34	30, 343, 000	1.79	230, 000	. 76
Total Texas	16	36	434, 889, 000	14, 968, 000	3. 44	299, 479, 000	1.45	3, 303, 000	1.10
Total United States.	21	50	574, 006, 000	19, 547, 000	3. 41	335, 533, 000		4, 338, 000	1. 29

<sup>&</sup>lt;sup>1</sup> In counting the total number of producers reporting, a producer operating in more than 1 State, district, or county is counted but once.

Twenty-five percent of the total output in 1942 was produced by furnace processes, 17 in 1941, 13 in 1940, and 11 in 1939. In October 1942 the War Production Board placed furnace blacks under strict allocation control.

Increased production of these high-yield blacks raised the average yield for the United States to a new peak of 1.71 pounds per thousand cubic feet of gas, compared with 1.63 in 1941 and 1.54 in 1940.

Number and capacity of plants.—One plant was shut down in Stephens County, Tex., in 1942, and one new plant was operated in Lea County, N. Mex., and one in Contra Costa County, Calif.—making a total of 50, compared with 49 in 1941.

The total daily capacity of all plants was 1,808,756 pounds compared with 1,716,395 in 1941, a 5-percent gain. It is estimated that plants operated at 87 percent of capacity compared with 95 percent in 1941.

Producers.—The Shell Chemical Co., with a plant in Contra Costa County, Calif., was added to the list of carbon-black producers during the year; otherwise the list remains unchanged from 1941.

# Carbon-black producers of the United States, as of December 31, 1942

State and company	County or parish	Nearest town	Process
California: Shell Chemical Co	Contra Costa	Pittsburg	Furnace.
Kansas:	G	Ulysses	"Special."
Peerless Carbon Black Co		Ulysses	
United Carbon Co., Inc	do	Ryus	Roller.
Louisiana:	Ouachita	Sterlington	Channel.
Imperial Oil & Gas Products Co Charles Eneu Johnson & Co	Morehouse	Bastrop.	Do.
		Bourland	"Special."
Peerless Carbon Black Co Southern Carbon Co		Hancock	Lewis.
Thermatomic Carbon Co		Sterlington	Thermatomic.
Thermatomic Carbon Co	do	Swartz	Channel.
United Carbon Co	Lea	Eunice	Do.
	Lea	Eumce	D0.
Oklahoma:	Seminole	Wewoka	Do.
Cabot Carbon Co General Atlas Carbon Division of	Texas	Guymon	Furnace.
	1 cass	Guymon	rumace.
General Properties Co., Inc. Charles Eneu Johnson & Co	Dominator	Stonewall	Channel.
	Pontotoc Beckham		
United Carbon Co	Becknam	Sayre	Do.
Texas:	G	Clro11-rto-rem	Roller and channel
Cabot Carbon Co	Carson	Skellytown	
	Gray	Pampa	Channel.
	Hutchinson	Stinnett	Do.
	Ward	Monahans	Do.
	Winkler	Kermit	Do. Roller.
Carbon Blacks, Inc	Gray	Pampa	
Coltexo Corporation	do	Lefors	Channel.
Columbian Carbon Co	Carson 1	(1)	(1).
	Gray	Kings Mill	Channel.
	do	Lefors	Do.
	Hutchinson	Borger (2 plants 1)	Do. Do.
	Moore	Sunray	
3	Nueces	Corpus Christi	Do.
a m a	Wheeler	Lela	Do.
Columbian-Phillips Co	Moore	Sunray	
Combined Carbon Co	Hutchinson	Sanford	Do.
Continental Carbon Co	Moore	Sunray	Do.
Crescent Carbon Co	Hutchinson	Borger	Do.
Crown Carbon Co	Moore	Sunray	_ Do.
General Atlas Carbon Division of	Gray	Pampa	Furnace.
General Properties Co., Inc.			<b>~</b> 1
J. M. Huber Corporation	Hutchinson	Borger	Channel.
Moore County Carbon Co	Moore	Sunray	Do.
Panhandle Carbon Co	Hutchinson	Borger	Do
Peerless Carbon Black Co	Gray	Pampa	"Special."
Texas Elf Carbon Co	do	do	Channel.
	Stephens	Eliasville	Do.
United Carbon Co	Aransas	Aransas Pass	_ Do.
	do	do	Furnace.
	Hutchinson	Borger (3 plants)	Channel.
	do	Sanford (2 plants)	Do.
	do	Stinnett	Do.
	Moore	Sunray (2 plants)	Do.

<sup>1</sup> Plant, located in both Carson and Hutchinson Counties, counted in Hutchinson County.

## DEMAND

Total deliveries.—Carbon-black deliveries reported by producers were 449,931,000 pounds during 1942 compared with 644,744,000 pounds in 1941. There was a sharp decline both in exports and in

all major classes of domestic sales. (See fig. 2.)

Domestic consumption.—Domestic deliveries totaled 334,296,000 pounds in 1942 compared with 496,579,000 pounds in 1941, a 33-percent decline. Sales to the major classes of consumers were: Rubber companies, 295,947,000 pounds (88 percent); ink companies, 19,233,000 pounds (6 percent); paint companies, 3,616,000 pounds (1 percent); and miscellaneous, 15,500,000 pounds (5 percent). These quantities are in virtually the same ratio to total sales as in 1941.

The curtailment in the rubber industry caused a 33-percent decline in movements to rubber companies. Trade was light up to the middle of the year, when there was a slight improvement. Toward the end of the year deliveries to synthetic rubber manufacturers strengthened the market.

Before the war, when supplies of natural rubber were ample, channel blacks dominated the rubber markets at the expense of furnace blacks. The finer-grained, harder channel blacks were superior in a brasive resistance, which gave them a decided advantage in the manufacture of the average automobile tire, which, in normal times, constitutes the most




FIGURE 2.—Production and consumption of carbon black, 1933-42. Production in "Texas other than Panhandle" included in "Other States," 1933-35.

important part of the carbon-black market. The only reason furnace blacks survived this competition was their relatively high yield.

When most of the sources of natural rubber were cut off and the synthetic rubber program was projected, the picture changed radically. Most grades of synthetic rubber have higher heat generation and lower tensile strength than natural rubber. Both of these general characteristics call for the use of large amounts of the softer, coarser-grained blacks, which explains why the present trend in construction is toward furnace-type blacks and away from channel blacks.

Sales to ink companies amounted to 19,233,000 pounds in 1942 compared with 28,198,000 in 1941. As the quantity of newsprint available for consumption in 1942 was only 3 or 4 percent below 1941, it is apparent from the sales figures that the ink companies did considerable stocking in 1941.

The paint trade was affected by the curtailment in automobile manufacture and the consequent declines in the use of black paints and enamels. Paint companies purchased 3,616,000 pounds of carbon black in 1942, a 38-percent decline from the 1941 figure (5,840,000).

pounds).

Deliveries for miscellaneous purposes totaled 15,500,000 pounds in 1942, a 33-percent decline from the 1941 record of 23,039,000 pounds.

Exports and imports. Exports of carbon black in 1942 continued the decline started in 1940, when the war began to impair foreign trade. A total of 115,635,000 pounds was purchased by foreign countries during the year, a 22-percent decrease from the 148,165,000 pounds purchased in 1941 and a 43-percent decrease from the peak of 203,828,000 pounds recorded in 1939. The total value was \$5,229,000 in 1942 and \$6,686,000 in 1941, an average of 4.52 and 4.51 cents per pound, respectively. The average for the year 1940 was 4.40 cents.

The United Kingdom continued to be the leading customer, purchasing 58,223,000 pounds (39 percent of the total) in 1941 and 53,297,000 pounds (46 percent of the total) in 1942. Canada ranked second, with 32,760,000 pounds purchased in 1941 and 29,651,000 in

1942.

September was the month of heaviest shipments in 1941 and June in 1942. Galveston, which has been the main shipping point for a number of years, dropped from 115,042,000 pounds exported in 1940 to 61,132,000 in 1941 and to 22,914,000 in 1942. Michigan took first place in 1942 with 29,085,000 pounds shipped out.

Carbon black exported from the United States, 1941-42, by months and customs districts

	1941		194:	2	Customs dis-	19	41	19	12
Month	Pounds	Value	Pounds	Value	trict	Pounds	Value	Pounds	Value
Apr May June July Aug Sept Oct	12, 119, 912 10, 808, 292 12, 502, 252	384, 618 538, 411 508, 468 683, 493 298, 292 670, 866 503, 884 1, 061, 790 545, 162 449, 696 586, 945	15, 789, 105 5, 144, 342 11, 252, 102 9, 598, 078	618, 850 255, 541 391, 223 224, 609 767, 683 215, 649 537, 347 436, 866 212, 930 463, 865 408, 140	Los Angeles Michigan New Orleans New York Sabine San Francisco Vermont Other districts	362, 540 32, 286, 372 28, 625, 209 3, 001, 380 11, 100 3, 886, 606 124, 486 16, 484, 901	1, 557 80, 550 2, 982, 173 14, 261 1, 091, 563 1, 386, 931 170, 394 616 166, 578 5, 031 774, 378	248, 360 1, 885, 776 22, 913, 733 2, 725, 617 29, 084, 820 14, 742, 059 16, 849, 264 5, 341, 767	9, 123 79, 243 1, 081, 536 38, 798 1, 045, 644 786, 987 863, 151 268, 930 2, 236 1, 042, 624

<sup>&</sup>lt;sup>1</sup> Figures on exports and imports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Carbon black	ernorted	from the	United States,	1010-10 7	ni anzimimian
Car con chach	Cwp OI VOW	J1 0110 0100	O more woulds,	1040-40, 0	u countines

Country	194	10	1941		1942	
	Pounds	Value	Pounds	Value	Pounds	Value
The second secon	0.005.001	****		****		
Argentina	3, 005, 361	\$150, 558	5, 828, 519	\$287,870	3, 215, 276	\$161, 503
Australia	7, 264, 539	327, 434	12, 201, 171	563, 104	7, 833, 813	405, 850
Belgium	1, 251, 212	66, 172				
Brazil	2, 181, 849	99, 911	6, 235, 139	285, 204	2, 626, 163	131, 840
Canada	19, 622, 401	592, 885	32, 760, 178	1, 118, 151	29, 650, 763	1, 070, 714
China	1, 860, 072	90, 133	486, 667	24, 126		
France	24, 397, 155	1, 122, 773		<b></b>		
India and Dependencies 1	3, 825, 436	182, 939	6, 768, 852	305, 699	7, 648, 607	354, 672
Italy Japan	4, 547, 708	204, 375				
	17, 662, 686	785, 760	2, 274, 000	98, 447		
Mexico	1, 826, 648	67, 187	2, 250, 143	93, 742	4, 841, 480	133, 163
Netherlands	1, 114, 599	57, 919				
Netherlands Indies	1, 463, 111	78, 327	2, 780, 458	129, 017	756, 075	44, 458
Norway Portugal	538, 454	24, 138				
Portugal	1, 645, 097	74, 474	140, 762	8, 767	84, 997	5, 547
Spain	483, 770	22, 243	818, 500	37, 451	565, 150	28, 047
Sweden	1, 281, 550	59, 882	345, 550	17, 440	265, 275	17, 486
Union of South Africa	4, 025, 531	182, 900	7, 668, 759	345, 536	2, 618, 460	126, 396
United Kingdom 2	77, 308, 549	3, 503, 191	58, 223, 076	2, 889, 741	53, 296, 513	2, 608, 449
Other countries	2, 312, 139	130, 619	9, 383, 523	482, 017	2, 232, 585	141, 019
	177, 617, 867	7, 823, 820	148, 165, 297	6, 686, 312	115, 635, 157	5, 229, 144

<sup>&</sup>lt;sup>1</sup> British India.

Imports of "gas black and carbon black" rose from 800 pounds valued at \$101 in 1941 to 77,870 pounds valued at \$7,307 in 1942. Acetylene black imported from Canada declined from 4,063,000 pounds valued at \$430,000 in 1941 to 3,840,000 pounds valued at \$381,000 in 1942.

#### STOCKS

Stocks at the end of the year more than doubled the 118,847,000 pounds reported on hand December 31, 1941. A 3-percent decrease in production and a 30-percent decrease in sales caused supplies to accumulate until they totaled 242,755,000 pounds by the end of 1942. This was the highest year-end total since 1932, when 257,998,000 pounds were reported.

## PRICES AND VALUES

The average value of carbon black at the plants in 1942 was 3.41 cents, a gain of 0.15 cent over 1941. Prices remained unchanged during the year, except for a small advance during the first week of January. This rise (0.2 cent) brought the quotation for regular, uncompressed black, in bags at the plants, to 3.625 cents a pound.

<sup>2</sup> United Kingdom of Great Britain and Northern Ireland.

# ASPHALT AND RELATED BITUMENS

By A. H. REDFIELD 1

#### SUMMARY OUTLINE

	Page		Page
Summary Native asphalts and bitumens Bituminous rock Gilsonite and wurtzilite Sullonated bitumen Exports	1185 1185 1185 1185 1185	Production Stocks Sales Foreign trade Distribution by rail	1186 1186 1187 1187 1190 1190
		Road oil	1192

#### SUMMARY

Refinery sales of petroleum asphalt (exclusive of road oil) to domestic consumers in the United States were 10 percent larger in tonnage in 1942 than in 1941; and, because of higher prices, they were 17 percent larger in value. As the refinery output was 4 percent less than in 1941 and imports were 22.5 percent lower, inventories at the refineries were reduced nearly one-third, and more of the other petroleum products were transferred to the asphalt account. Exports in 1942 were only 38 percent as large as those in 1941.

As in 1941, the tonnage of bituminous rock sold increased more proportionally—43 percent—than did the total tonnage of solid and liquid asphalt sold for paving purposes—10 percent. Although the comparatively low valued products of Texas and Oklahoma supplied the greater increases in sales of bituminous rock, the total value of bituminous rock sold increased 46 percent, and the average value per

short ton was 2 percent higher.

#### NATIVE ASPHALT AND BITUMENS

Bituminous rock.—Sales of rock asphalt by producers in the United States increased 43 percent in quantity—from 654,692 short tons in 1941 to 935,295 tons in 1942—and 46 percent in value—from \$2,312,-227 to \$3,367,279. Prices were higher than in 1941, and the average

sales value at the mine increased from \$3.53 to \$3.60 per ton.

Texas and Oklahoma operators increased their sales from 446,432 tons valued at \$1,197,319 in 1941 to 699,572 tons valued at \$2,018,822 in 1942. Sales were larger also in California and in Missouri. East of the Mississippi River, producers in Kentucky and Alabama enlarged their sales from 193,887 tons valued at \$1,047,529 in 1941 to 207,324 tons valued at \$1,228,748 in 1942.

Gilsonite and wurtzilite.—Increased demand in the domestic market raised producers' sales of gilsonite in Utah from 36,407 tons valued at \$851,623 in 1941 to 40,041 tons valued at \$909,311 in 1942. The average sales price per ton at the mine or railhead decreased from \$23.39

to \$22.71.

Sales of wurtzilite from Utah decreased from 69 tons valued at

\$5,343 in 1941 to 37 tons valued at \$2,852 in 1942.

Sulfonated bitumen.—Sales of natural sulfonated bitumen from Box Elder County, Utah, were considerably larger in 1942 than in 1941.

Exports.—Exports of natural unmanufactured asphalt amounted to 10,865 short tons valued at \$328,660 in 1941 and to 8,941 tons valued at \$231,772 in 1942. Increased sales to Canada, Australia,

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

and the United Kingdom did not compensate for decreased exports to Brazil and complete cessation of shipments to Japan and to China.

# MANUFACTURED OR PETROLEUM ASPHALT

Production.—Production of asphalt by petroleum refineries in the United States decreased 4 percent from 1941. In the East Coast district output decreased 62 percent, because wartime difficulties of transport reduced the total runs of crude petroleum by 26 percent, and higher proportions of the reduced runs were made into residual and distillate fuel oil. Slightly less asphalt was made in refineries of the Indiana-Illinois-Kentucky-etc. district also than in 1941. On the other hand, increased production of asphalt in the other refining districts almost offset the sharp decrease in the East Coast district. The most marked increase in asphalt tonnage was in California, where 50 percent more asphalt was made in 1942 than in 1941.

Production, receipts, stocks, consumption, transfers, losses, exports, and domestic sales of asphalt (exclusive of road oil) at petroleum refineries in the United States in 1942, by districts, in short tons

		Receipts	Sto	ocks	Consump- tion by	Sales to
District	Produc- tion	from other sources	Dec. 31, 1941	Dec. 31, 1942	companies, transfers, losses, and exports	domestic consumers
East Coast	817, 200	120, 500	120,000	50,000	24, 900	982, 800
	339, 300	700	13,000	26,400	10, 700	315, 900
	1, 322, 400	158, 700	171,000	96,700	347, 600	1, 207, 800
	526, 700	97, 300	94,000	39,600	39, 800	638, 600
Texas: Gulf Coast Inland Total Texas	497, 600 388, 300 885, 900		23,000 15,000 38,000	23, 800 20, 200 44, 000	85, 800 20, 300 106, 100	411,000 362,800 773,800
Louisiana-Arkansas: Louisiana Gulf Coast Arkansas and Louisiana Inland	519, 800	32, 700	47, 000	38, 000	25, 400	536, 100
	370, 100	25, 800	22, 000	22, 000	2, 500	393, 400
Total Louisiana-Arkansas	889, 900	58, 500	69,000	60,000	27, 900	929, 500
Rocky Mountain	178, 900	181, 000	27,000	18,500	3, 500	364, 900
California	1, 336, 200	434, 200	72,000	75,800	139, 100	1, 627, 500
Total United States:	6, 296, 500	1,050,900	604, 000	411, 000	699, 600	6, 840, 800
19421941	6, 557, 600	653,100	614, 000	604, 000	992, 000	6, 228, 700

Sales of asphalt (exclusive of road oil) at petroleum refineries to domestic consumers in the United States, 1941-42, by districts

D14.14	19	41	1942		
District	Short tons	Value	Short tons	Value	
East Coast	2, 165, 783	\$24, 799, 304	982, 821	\$13, 117, 302	
	249, 362	3, 071, 753	315, 883	4, 243, 253	
	1, 026, 016	10, 506, 007	1, 207, 744	13, 334, 239	
	620, 166	4, 373, 066	638, 618	5, 296, 640	
	196, 015	1, 773, 130	411, 042	4, 455, 867	
	336, 022	2, 948, 610	362, 809	3, 531, 567	
	532, 037	4, 721, 740	773, 851	7, 987, 434	
Louisiana-Arkansas: Louisiana Gulf Coast. Arkansas and Louisiana Inland Total Louisiana-Arkansas. Rocky Mountain California. Total United States.	363, 885	3, 496, 201	536, 107	6, 109, 670	
	315, 116	2, 210, 082	393, 404	3, 202, 112	
	679, 001	5, 706, 283	929, 511	9, 311, 782	
	161, 200	1, 492, 574	364, 900	3, 589, 734	
	795, 158	5, 842, 416	1, 627, 453	13, 934, 917	
	6, 228, 723	60, 513, 143	6, 840, 781	70, 815, 301	

Stocks.—The heaviest relative drafts on stocks were at East Coast refineries. Stocks were reduced also during 1942 in the Indiana-Illinois-Kentucky-etc., the Oklahoma-Kansas-Missouri, the Louisiana Gulf Coast, and the Rocky Mountain districts. On the other hand. more asphalt was in storage at the end of 1942 in the Appalachian district in Texas, and in California.

Sales.—Sales of petroleum asphalt by refineries to domestic consumers in the United States increased 10 percent in quantity and 17 percent in value from 1941 to 1942; the average value at the refinery

increased from \$9.72-per short ton to \$10.35.

Of the total sold, 7 percent was manufactured from foreign petroleum (imported chiefly from Venezuela and Mexico) in 1942, compared with 25 percent in 1941. Although runs of foreign crude oil to stills decreased 71 percent, sales of petroleum asphalt from this source decreased only 68 percent. Of the foreign crude processed, 17 percent was converted into asphalt in 1941 and 21 percent in 1942. East Coast refineries sold 88 percent of the total asphalt made from

foreign crude in 1942 compared with 97 percent in 1941.

Highway and street construction and airport-runway surfacing used (in the form of paving asphalt, paving flux, cut-back asphalts, and asphalt emulsions) 64 percent of the total asphalt sold to domestic consumers by petroleum refineries in 1942 as in 1941. Street and road contracts exceeding \$25,000, compiled by Engineering News-Record. show a decrease of 9 percent in value—from \$582.8 million in 1941 to \$530.5 million in 1942—and of 14 percent in indicated volume if the values are adjusted by the Engineering News-Record index of construc-Contracts awarded in New England and 5 Middle Atlantic States decreased sharply and were considerably lower in 14 States lying west of Mississippi River and east of the Rocky Mountains. On the other hand, more roadway was contracted for in 10 Southeastern States and Louisiana in 1942 than in 1941; and in 7 Far Western States a sharp increase in highway contracts occurred.

Asphalt and asphaltic material (exclusive of road oil) sold at petroleum refineries to domestic consumers in the United States in 1942, by varieties

Variety		lomestic oleum		foreign bleum	Total	
,	Short tons	Value	Short tons	Value	Short tons	Value ·
Solid and semisolid products of less than 200 penetration:  Asphalt for— Paving Roofing Waterproofing Blending with rubber Briquetting Mastic and mastic cake Pipe coatings. Molding compounds Miscellaneous uses.	1, 969, 676 1, 176, 715 85, 503 14, 877 97, 812 6, 997 15, 337 32, 949 184, 454	\$19, 458, 316 11, 917, 708 1, 078, 263 238, 376 964, 383 93, 317 233, 921 447, 535 2, 067, 264 36, 499, 083	163, 538 123, 453 7, 922 7, 386 5, 185 5, 185 5, 189 3, 179 29, 586 340, 847	\$2, 114, 510 1, 600, 525 123, 931 120, 401 72, 590 9, 460 44, 453 447, 573 4, 533, 443	2, 133, 214 1, 300, 168 93, 425 22, 263 97, 812 12, 182 16, 935 36, 128 214, 040 3, 925, 167	\$21, 572, 82 13, 518, 23 1, 202, 19 964, 38 165, 90 243, 38 491, 98 2, 514, 83 41, 032, 52

[Value f. o. b. refinery]

Asphalt and asphaltic material (exclusive of road oil) sold at petroleum refineries to domestic consumers in the United States in 1942, by varieties—Continued

[Value f. o. b. refinery]

Variety		From domestic petroleum		foreign oleum	Total	
	Short tons	Value	Short tons	Value	Short tons	Value
Semisolid and liquid products of more than 200 penetration:						
Paving Roofing Waterproofing	326, 705 533, 443 21, 892	\$2, 344, 655 4, 108, 916 156, 914	17, 713 35, 847 431	\$235, 756 451, 723 5, 603	344, 418 569, 290 22, 323	\$2,580,411 4,560,639
Mastic Cut-back asphalts:	4,050	37, 229			4,050	162, 517 37, 229
Rapid-curing  Medium-curing  Emulsified asphalts and fluxes Paints, enamels, japans, and	689, 319 998, 811 117, 803	7, 639, 637 11, 033, 843 1, 458, 862	53, 593 47, 247 842	822, 350 617, 486 22, 790	742, 912 1, 046, 058 118, 645	8, 461, 987 11, 651, 329 1, 481, 652
lacquersOther liquid products	35, 702 25, 625	644, 768 89, 602	6, 576 15	112, 491 150	42, 278 25, 640	757, 259 89, 752
	2, 753, 350	27, 514, 426	162, 264	2, 268, 349	2, 915, 614	29, 782, 775
Total: 1942 1941	6, 337, 670 4, 676, 218	64, 013, 509 42, 408, 215	503, 111 1, 552, 505	6, 801, 792 18, 104, 928	6, 840, 781 6, 228, 723	70, 815, 301 60, 513, 143

Paving asphalt sold at petroleum refineries to domestic consumers in the United States, 1941-42, by districts, in short tons

	and the second s		
	District	1941	1942
East Coast Appalachian Indiana, Illinois, Kentucky, e Oklahoma, Kansas, and Misse	te	 779, 923 66, 940 178, 549 36, 526	292, 884 67, 234 254, 467 92, 987
Inland		 45, 575 64, 361	118, 372 144, 847
		 109, 936	263, 219
Louisiana-Arkansas: Louisiana Gulf Coast Arkansas and Louisiana Is	nland	 145, 953 143, 562	192, 041 163, 591
Rocky Mountain	as	 289, 515 26, 773 276, 059	355, 632 112, 177 694, 614
Total United States		 1, 764, 221	2, 133, 214

Nevertheless, sales of paving asphalt, used for high-type surfacing, increased 21 percent over 1941. The East Coast district was the only exception to the general increase. Government purchases rather than private contracts apparently caused these increases.

A marked drop in sales of cut-back asphalts by East Coast refineries was the principal factor in the 6-percent decline in total sales of these products. Sales of cut-backs were more than one-third less than in 1941 in the Oklahoma-Kansas-Missouri district also. In other refining districts sales of cut-back asphalts increased markedly, indicating an increase in light highway construction, except on the East coast and in central United States.

Cut-back asphalts sold at petroleum refineries to domestic consumers in the United States, 1941-42, by districts, in short tons

District	1941	1942
East Coast	576, 779 46, 526 280, 437 323, 115	118, 371 57, 073 311, 618 205, 506
Texas: Gulf Coast Inland Total Texas	75, 305 65, 753 141, 058	128, 579 77, 695 206, 274
Louisiana-Arkansas: Louisiana Gulf Coast	143, 544 48, 507	172, 716 51, 965
Total Louisiana-Arkansas	192, 051 114, 739 228, 427	224, 681 225, 890 439, 557
Total United States	1, 903, 132	1, 788, 970

More emulsified asphalts were sold in 1942 than in 1941. Petroleum refineries sold 129,006 short tons (30,396,265 gallons) valued at \$1,576,840 in 1941 and 118,645 tons (27,955,076 gallons) valued at \$1,481,652 in 1942; in addition, 76,830,549 gallons valued at \$6,919,102 in 1941 and 86,973,381 gallons valued at \$8,996,057 in 1942 were sold by major industrial companies that purchased asphalt from petroleum refineries. Accordingly, total known sales of emulsified asphalts and fluxes increased 7 percent in quantity—from 107,226,814 gallons to 114,928,457 gallons—and 23 percent in value—from \$8,495,942 to \$10,477,709.

Roofing manufacture made the second-largest demand for asphalt, absorbing 27 percent of the total sales to domestic consumers in both 1941 and 1942. Although shipments of prepared roofing and asphalt siding reported to the Bureau of the Census increased 26 percent—from 44,275,100 squares (revised figure) in 1941 to 55,967,441 squares in 1942—domestic sales of roofing asphalt and roofing flux combined increased only 12 percent—from 1,671,696 to 1,869,458 tons.

Roofing asphalt and flux sold at petroleum refineries to domestic consumers in the United States, 1941–42, by districts, in short tons

District	1941	1942
East CoastAppalachian	513, 927 120, 515 430, 365 136, 196	402, 561 164, 003 480, 430 217, 178
Texas: Gulf Coast Inland	35, 603 79, 652	106, 210 90, 183
Total Texas	115, 255	196, 393
Louisiana-Arkansas: Gulf Coast	32, 757 116, 142	62, 981 64, 987
Total Louisiana-Arkansas	148, 899 3, 789 202, 750	127, 968 3, 849 277, 076
Total United States	1, 671, 696	1, 869, 458

## FOREIGN TRADE

Imports.—Imports of natural asphalt and bitumen into the United States in 1942 totaled 7,961 short tons valued at \$136,054 compared with 13,543 tons valued at \$182,723 in 1941. Imports of lake asphalt from Trinidad decreased from 8,593 tons valued at \$93,708 in 1941 to 6,122 tons valued at \$79,817 in 1942, and imports of grahamite from Cuba decreased from 4,682 tons valued at \$83,859 to 1,351 tons valued at \$24,741.

Imports of solid petroleum asphalt increased slightly—from 66,352 tons valued at \$243,306 in 1941 to 68,638 tons valued at \$309,140 in 1942. All the 1941 imports and 66,505 tons (valued at \$282,395) of those in 1942 came from Netherlands West Indies.

In addition, 434,839 barrels (79,062 tons) valued at \$243,306 of liquid petroleum asphalt, including cut-backs and road oil, were imported in 1941 and 255,934 barrels (46,533 tons) valued at \$370,606 Mexico supplied all the imports in 1941 and 255,418 barrels

(46,439 tons) valued at \$369,088 of those in 1942.

Exports.—War blockades and the disruption of normal ocean traffic caused exports of petroleum asphalt from the United States to drop from 224,798 short tons valued at \$3,689,502 in 1941 to 85,205 tons valued at \$1,645,353 in 1942. The only exceptions to the general decline were in points of special war activity of the United States, such as Panama Canal Zone, Gold Coast, and Nigeria.

## DISTRIBUTION BY RAIL

The tonnage of asphalt (natural, byproduct, or petroleum) terminated by class I and class II railroads within the United States decreased from 6,879,488 tons in 1941 to 6,152,459 tons in 1942, according to freight-commodity statistics compiled by the Interstate Commerce Commission. Increased deliveries in the Pacific, Mountain, and West South Central States failed to offset smaller deliveries east of Mississippi River and in the West North Central States.

Asphalt (natural, byproduct, or petroleum) terminated by class I railroads in the United States, 1941-42, by States, in short tons

• State and group	1941	1942
New England	297, 920	156, 180
Aiddle Atlantic:		
New York	313, 212	164, 041
New Jersey	137 882	101, 450
remsylvania	718, 705	397, 167
Total Middle Atlantic	1, 169, 799	662, 658
East North Central:		
Ohio	1, 235, 174	1, 105, 741
Indiana	358 333	288, 242
Illinois	618,655	507, 244
Michigan	203, 626	128, 353
		138, 230
Total East North Central	2, 618, 108	2, 167, 810
Vest North Central:		
Minnesota	117, 399	86, 507
Iowa		35, 297
Missouri North Dakota	127, 455	88, 515
South Dakota		22, 964
Nebraska	33, 386 50, 791	51, 363 45, 907
Kansas	71, 978	55, 652
Total West North Central	474, 206	386, 205

Asphalt (natural, byproduct, or petroleum) terminated by class I railroads in the United States, 1941-42, by States, in short tons—Continued

State and group	1941	1942
South Atlantic:		
Delaware	18,739	18, 83
Maryland	34,079	26, 34
District of Columbia.	9,898	6, 38
	136, 696	71, 88
	80,991	57, 05
West Virginia	. 126, 818	77, 18
North Carolina		38, 0
South Carolina	57, 747 87, 806	84. 14
Georgia	100,000	128, 3
Florida	106, 235	128, 36
Total South Atlantic	659, 009	508, 22
East South Central:		
Kentucky	95, 341	62, 52
Tennessee	102, 144	85, 5
Alabama	70,578	80, 32
Mississippi	57, 516	68, 4
Total East South Central	325, 579	296, 8
West South Central:		
Arkansas	27, 308	52, 2
Louisiana	117, 236	121, 9
Oklahoma	28, 983	20, 14
Texas	189, 128	245, 50
Total West South Central	362, 655	439, 85
Mountain:		
Montana	12,612	71, 59
Tdaho	29, 137	37.4
Wyoming	14,886	23, 9
Colorado	65, 309	99, 30
New Mexico	41, 208	61, 5
Arizona	54, 020	162, 6
	22, 042	39, 88
Utah Nevada	35, 096	58, 70
Total Mountain	274, 310	555, 19
Doolfat		
Pacific: Washington	90, 274	122, 78
W asing tou	73, 801	132, 22
Oregon	372, 364	543, 68
California	372,304	
Total Pacific	536, 439	798, 60
Total United States	6, 718, 025	5, 971, 6
Canada	4,806	1,30

Source: Interstate Commerce Commission, Freight Commodity Statistics.

## ROAD OIL

Refinery sales of road oil to domestic consumers decreased 19 percent in quantity in 1942. Only 31,325 barrels valued at \$58,371 were manufactured from foreign crude. Of this total 18,858 barrels valued at \$28,406 were sold by refineries of the East Coast district, and nearly all the remainder was sold by refineries of the Rocky Mountain district.

Road oil sold by petroleum refineries to domestic consumers in the United States, 1941-42, by districts

	19	141	19	142
District	Thousands	Thousands	Thousands	Thousands
	of barrels	of dollars	of barrels	of dollars
East Coast. Appalachian Indiana, Illinois, Kentucky, etc. Oklahoma, Kansas, and Missouri Texas Louisiana-Arkansas Rocky Mountain California	391	1, 542	106	192
	44	77	31	71
	2, 603	3, 683	1, 278	1, 968
	682	1, 101	360	529
	237	368	80	127
	121	127	17	56
	1, 458	1, 851	1, 197	1, 729
	3, 295	3, 503	4, 058	4, 931
Total United States	8, 831	12, 252	7, 127	9, 603

Production, receipts, stocks, consumption, transfers, losses, exports, and domestic sales of road oil in the United States in 1942, by districts, in thousands of barrels

	1	Receipts	Sto	eks	Consump-	
District	Produc- tion	from other sources	Dec. 31, 1941	Dec. 31, 1942	companies, transfers, losses, and exports	Sales to domestic consumers
East Coast	-5 30	74	39	1	1	106 31
Indiana, Illinois, Kentucky, etc Oklahoma, Kansas, and Missouri	1, 169 396	39 217	168 32	13 34	85 251	1, 278 360
Texas Louisiana-Arkansas Rocky Mountain	48 149 1, 363	49 1 263	35 15 252	51 15 117	1 133 564	80 17
California.	4, 889	205	251	117	965	1, 197 4, 058
Total: 1942 1941	8, 039 9, 149	643 514	793 624	348 793	2, 000 663	7, 127 8, 831

# **CEMENT**

# By Forrest T. Moyer and E. V. Balser

#### SUMMARY OUTLINE

	Page		Page
Summary	1193	Portland cement—Continued.	
Salient statistics	1194	Raw materials	1213
Portland cement	1197	Fuels and power	. 1214
Production, shipments, and stocks	1197	Special cements	1215
Domestic consumption	1203	New developments	1216
Local supplies	1208	Natural, masonry (natural), and puzzolan	l .
Transportation	1208	cements	1217
Prices	1210	Foreign trade	1217
Capacity of plants			
Clinker production	1212		1218
Production according to raw materials	1212	World production	

## SUMMARY

Production of finished hydraulic cements in 1942, the construction year of the war program, advanced to a new record of 185,341,609 barrels—a total that surpassed 1941 output by 11 percent and the former high set in 1928 by 4 percent. The gain over 1941 resulted entirely from the record demand for portland cement as output of natural and other hydraulic cements, which represent only a small percentage of the total, declined slightly. Total shipments from producing mills in 1942 reached a new high volume of 187,809,208 barrels and exceeded production by nearly 2½ million barrels. As a result, stocks of finished cement at mills on December 31, 1942, fell to 17,696,686 barrels, a 12-percent decline from stocks at the end of 1941. Reflecting increased costs of production over 1941, the average mill value of portland cement rose 6 cents to \$1.53 per barrel and that

for all other hydraulic cements advanced 10 cents to \$1.46. Although private and defense construction had begun to taper off in the latter part of 1941, the mounting volume of construction contracted after the country entered the war in December had almost immediate effect upon the cement industry. Over-all activity, after allowance for seasonal effects, increased rapidly to a peak in the August-October period of 1942. Production of cement advanced from the low monthly volume of the year in February to a peak in October with only minor recessions during June and September. Through November and December output was maintained at a relatively high level in order to replenish the badly depleted stocks. Monthly shipments increased rapidly from February through August and remained at a high level to the end of October. However, in November and December shipments declined at a slightly more than seasonal rate. During January-March stocks of finished cement were built up to a normal level of about 25 million barrels, which was maintained through May. In the June-October period, when shipments greatly exceeded production, stocks declined rapidly to a low on October 31 of slightly less than 11 million barrels, but by the end of December these had been restored approximately halfway to the

customary level.

Requirements exceeded supplies in some sections of the country, and cement had to be brought in from relatively distant plants. However, there were few shipments of large quantities for unusually long distances. Shortages developed during 1942 in the Southeastern States, Texas, and Washington. Temporary shortages were apparent in Kansas and Nebraska.

Salient statistics of the cement industry in the United States, 1938-42

	1938 1	1939	1940	1941	1942
Production of finished cement:					
Portland barrels Masonry, natural, and puzzolan (slag-	105, 357, 000	122, 259, 154	130, 216, 511	164, 030, 559	182, 781, 184
lime)barrels_	1, 820, 795	2, 439, 110	2, 534, 566	2, 875, 962	2, 560, 425
Total production do Capacity used at portland-cement	107, 177, 795	124, 698, 264	132, 751, 077	166, 906, 521	185, 341, 609
mills percent production of portland-cement	41. 2		I		
clinker 2 barrels Active plants:	104, 121, 105	121, 620, 018	130, 140, 932	163, 628, 857	181, 267, 461
Portland	151				
Masonry, natural, and puzzolan (slag- lime)	12	12	12	12	
Shipments from mills:					
Portland barrels Value 3	106, 324, 127 \$153, 977, 226	122, 651, 459 \$180, 893, 208	130, 349, 786	167, 439, 237	185, 300, 884
Per barrel Masonry, natural, and puzzolan (slag-	\$1.45	\$1.47	\$1.46	\$1.47	\$283, 237, 028 \$1. 53
lime) barrels barrels	1, 867, 949	2, 405, 135 \$3, 361, 724	2, 514, 597	2, 926, 203	2, 508, 324
Per barrel	\$1.46	\$3, 361, 724 \$1. 40	\$3, 386, 801 \$1. 35	\$3, 967, 567 \$1. 36	\$3, 668, 169 \$1. 46
Total shipmentsbarrels_	108, 192, 076	125, 056, 594	132, 864, 383	170, 365, 440	187, 809, 208
Stocks at mills, December 31: Portland:	\$156, 703, 002	\$184, 254, 982	\$193, 464, 869	\$250, 589, 481	\$286, 905, 197
Finished cement barrels	23, 992, 939	23, 645, 583	23, 364, 657	4 19, 964, 918	17, 445, 220
Clinker do Masonry, natural, and puzzolan (slag-	5, 286, 053	5, 165, 066	4, 885, 941	4, 574, 528	3, 509, 336
horrole	373, 816 1, 727, 411	239, 938 1, 913, 853	259, 868	199, 365	251, 466
Imports do Exports do Apparent consumption do	558, 226	1 140 000	538, 060 1, 667, 595	5 1, 757, 172	(6) (6) (6)
TT	109, 301, 201	125, 824, 108	131, 734, 848	(6)	. (6)

Does not include Puerto Rico, where production began in 1939.
 Compiled from monthly reports by producers.
 Value received f. o. b. mill, excluding cost of containers.

The strong demand for cement originated principally in the large volumes of military and industrial construction started in 1942. measured by Federal Reserve Board indexes (1923-25=100), based upon data of the Dodge Corporation, the value of construction contracts awarded in 1942 reached a new high of 166 compared with 122 in 1941 and 135, the former record, in 1928. The index for residential building declined from 89 in 1941 to 82 in 1942, whereas that for all other construction rose from 149 in 1941 to 235 in 1942. Engineering construction, which requires large quantities of cement, increased 59 percent over 1941, according to values of contracts reported by Engineering News-Record. The area of concrete pavement contracted for in 1942, as recorded by the Portland Cement Association, was 56

Figures cover January to September, inclusive. Figures not available for publication.

**CEMENT** 1195

percent greater than in 1941 and totaled nearly 132 million square yards. Airport paving was slightly more than treble the 1941 area and represented nearly three-fourths of the total pavement contracted in 1942, compared with slightly more than one-third in 1941. Road, street, and alley paving fell nearly one-third below the 1941 volume.

Distribution of consumption changed sharply in 1942, as indicated by the foregoing data. Direct military construction doubtless consumed most of the supply. In this category, the large volume of airport construction, coupled with the greater thicknesses of runways required to support the heavy planes, probably consumed more cement than any other type of construction. After military uses, the probable order of consumption was in construction of industrial plants and facilities, highways, and residential building. The first year of war also effected a marked change in location of cement consumption in the country (see fig. 2). As indicated by destinations of shipments from mills, consumption increased sharply over 1941 in the Southern and Rocky Mountain States and gained moderately in the Middle

and Pacific States but declined in the Northeastern States.

The first direct war control on the cement industry was the General Maximum Price Regulation of the Office of Price Administration, effective May 11. This order froze prices of cement at the highest selling value, f. o. b. plant, obtained during March 1942. Cement prices were removed from the general order by Maximum Price Regulation 188, which was effective August 1 and continued the March prices as maximum. With regard to cement prices, this order was superseded by Maximum Price Regulation 224, which applied only to cement and was effective September 23. Under the last regulation, prices on shipments within ordinary shipping radius of the mill were set at the maximum value obtained during the March 1-15 period, whether on a mill or delivered basis, plus any increase in freight rates since March 17. However, in order to insure adequate supplies in deficient areas, prices on shipments outside the normal shipping area of a mill were placed on an average dollars and cents f. o. b. basis determined for each Bureau of Mines district. For all districts other than California and Oregon and Washington the base was equal to 95 percent of the average net mill realization during 1941. two excepted districts the base was set at 95 percent of average net mill realization for the first quarter of 1942. This regulation provided for absorption of the extra and relatively high transportation costs by the consuming Government agencies.

As a means of increasing production and conserving grinding medium and power, similar emergency alternate specifications for three types of portland cement were formulated and approved early in June by the Federal Government and American Society for Testing Materials. War Production Board Limitation Order L-179, effective August 23, restricted manufacture of portland cement to the three types—general-purpose, moderate-heat, and high-early-strength—set forth in the emergency specifications. The order also prohibited assignment of storage bins for the exclusive use of any customer and required that all testing be done by the National Bureau of Standards or a Standards-approved laboratory. Twelve large dams in the Southern and Western States and oil-well cements were exempted from provisions of the orders.

On February 16, 1943, an amendment to this general limitation order removed the ban upon assignment of bin space to customers and no longer required that tests be done by an approved laboratory.

In addition to direct controls, the cement industry was affected by war restrictions on construction. The first of these, War Production Board Conservation Order L-41 of April 9 and its more restrictive revision of September 7, brought a virtual halt to all nonessential public and private construction as a means of assuring adequate labor and material supplies for necessary building. After the middle of 1942, the growing shortage of labor and raw materials forced recognition that construction was out of balance with other phases of the war




FIGURE 1.—Trends in production of hydraulic cements in the United States, 1885-1942.

program and that the country was being overbuilt. Consequently, the War Production Board on October 22 established the Facility Clearance Board and the Facility Review Committee to review construction already contracted and under way and also to approve all proposed construction for essentiality. By the end of 1942, stop orders had been issued on nearly 1½ billion dollars of contracts, of which much of the volume was for engineering construction that would have required large quantities of cement.

Since its inception in the early 1870's the portland cement industry has shown a remarkable rate of growth. By 1888 annual production had increased to 250,000 barrels, and from that time output gained

**CEMENT** 1197

rapidly in each year through 1913, when 92,097,131 barrels was produced. However, as shown in figure 1, the rate of increase flattened appreciably after 1910, and from 1913 through 1918 the industry suffered its first recession. The uptrend was resumed in 1919, and except for a minor setback in 1921 it continued at a substantial rate through 1928. In the depression of the early 1930's production slumped to 63,473,189 barrels (in 1933); and although recovery since then has been irregular, the over-all improvement, to the record output of 1942, has been rapid. Natural cement was first made in the United States near Chittenango, N. Y., in 1818. Combined annual production of it and miscellaneous hydraulic cements other than portland showed a generally rising trend to the record output of 10,203,179 barrels in 1899. Demand for portland exceeded that for other hydraulic cements for the first time in 1901, and as it continued to increase, demand for other cements declined to a low of 432,966 barrels Since then, annual production of hydraulic cements other than portland showed moderate recovery through 1928 followed by a sharp decline through 1932 and subsequent recovery to the 1941 output of 2,875,962 barrels.

#### PORTLAND CEMENT

### PRODUCTION, SHIPMENTS, AND STOCKS

As annual production of portland cement represents about 99 percent of the total output of all hydraulic cements, the general conditions affecting and the activity of the portland cement industry during 1942

were the same as those given in the preceding summary.

Location of war construction in 1942 effected marked changes in the quantities of portland cement produced in the various States. The record output of 1942 was obtained from 155 active mills in 35 States and Puerto Rico. Compared with 1941, production increased in 25 States and Puerto Rico, declined in 6 States, and was relatively unchanged in 4. Exceptional gains of more than one-third were recorded for Kansas, Oklahoma, South Dakota, Washington, and Puerto Rico. Ranking States in 1942, in order of output, were Pennsylvania, California, Texas, New York, and Michigan. Manufacture of cement ceased in New Jersey in 1942, and output declined sharply from 1941. Production was higher than in 1941 in all Bureau of Mines districts except New York and Maine, for which a small decline was recorded. The largest proportional gains were in the Western Missouri-Nebraska-Kansas-Oklahoma-Arkansas, Oregon-Washington, and Puerto Rico districts.

Shipments from mills during 1942 exceeded production in all districts except the Eastern Pennsylvania-New Jersey-Maryland, New York-Maine, Michigan, and Puerto Rico. As a result, these were the only districts in which stocks of finished cement at mills on December

31, 1942, were greater than at the end of 1941.

Finished portland cement produced, shipped, and in stock in the United States, 1941-42, by States and districts

		tive ints	Pı	roduction			•	Ship	oments from	mills				Stocks	at mills (I	Dec. 31)
			Bai	arreis		¥ .	1941 1942					_		Ba		
State and district	1941	1942	1941	1942	Per- cent of change from	Barrels	Value	)	Barrels	Value	)	cha from	ent of inge 1941	1941	1942 1	Percent of change from 1941
					1941		Total	Aver- age		Total	Aver- age	Bar- rels	Aver- age value		10.2	1011
STATE Alabama California Illinois Iowa Kansas Michigan Missouri New York Ohio Pennsylvania Puerto Rico <sup>3</sup> Tennessee Texas Other States <sup>4</sup>	25 1 6	12 4 5 6 11 5 11 9 24 2	5, 854, 218 5, 064, 620 4, 680, 630 9, 485, 147 6, 328, 003 11, 444, 508 8, 155, 704 32, 199, 184 462, 628 5, 588, 488 9, 679, 696	23, 350, 674 7, 049, 636 5, 062, 230 7, 254, 906 10, 615, 927 6, 971, 938 11, 067, 269 8, 181, 615 34, 114, 074 666, 698 6, 402, 291	+17.1 +20.4 05 +55.0 +11.9 +10.2 -3.3 +5.9 +44.1 +14.6 +25.3	20, 186, 028 5, 958, 376 5, 328, 398 4, 734, 129 9, 819, 218 6, 516, 345	8, 659, 014 7, 136, 933 13, 333, 855, 509 16, 073, 726 10, 657, 677 45, 383, 766 1, 005, 472 8, 520, 284 16, 362, 293	1. 33 1. 38 2. 16 1. 52	7, 726, 291 10, 349, 104 7, 397, 960 11, 027, 118 8, 652, 196 33, 639, 025 629, 358 6, 407, 196 12, 139, 800	11, 897, 607 46, 377, 469 1, 516, 075 9, 927, 895 20, 942, 867	1.38 1.38 2.41 1.55 1.73	+13.0 +17.8 +19.2 +63.2 +5.4 +13.5 -3.7 +7.9 +23.3 +35.3 +35.3 +35.3 +8.1	+3.8 +11.6 +2.0 -4.2	<b>3 400, 590</b>	780, 951 4, 803, 478 37, 642 395, 685 732, 284	-31. 9 -8. 4 -47. 1 -46. 5 +15. 7 -43. 1 +2. 3 -37. 6
DISTRICT	155	155	164, 030, 559	182, 781, 184 ————	+11.4	167, 439, 237	246, 621, 914	1. 47	185, 300, 884	283, 237, 028	1.53	+10.7	+4.1	2 19,964, 918	17, 445, 220	-12.6
Eastern Pennsylvania, New Jersey, and Maryland. New York and Maine. Ohio, western Pennsylvania, and West Virginia. Michigan. Wisconsin, Illinois, Indiana, and Kentucky	22 12 18 11	12 17 11	11, 995, 299 15, 153, 118 9, 485, 147	10, 615, 927	-2.4 +2.8 +11.9	12, 049, 832 15, 340, 784 9, 819, 218	43, 493, 559 17, 099, 278 20, 509, 369 13, 333, 850 24, 981, 549	1.34 1.36	11, 644, 827 16, 043, 856	22, 165, 074 14, 683, 683		-3. 4 +4. 6 +5. 4	+2.8 +3.0 +4.4	2 3, 694, 923 2 1, 851, 103 2 2, 438, 073 2 1, 700, 728 2 1, 614, 073	1, 913, 549 1, 967, 835 1, 967, 551	-19.3 +15.7

Virginia, Tennessee, Alabama, Georgia, Louisiana, and Florida	18	18	19, 982, 460	21, 808, 052	+9.1	20, 391, 422	30, 983, 258	1. 52	21, 864, 073	34, 063, 252	1. 56	+7.2	+2.6	2 1, 105, 818	1, 049, 797	-5.1
Eastern Missouri, Iowa, Minne- sota, and South Dakota Western Missouri, Nebraska,	11	11	11, 856, 659	12, 833, 837	+8.2	12, 443, 248	19, 990, 722	1.61	13, 896, 927	22, 058, 737	1. 59	+11.7	-1.2	<sup>2</sup> 2, 440, 004	1, 376, 914	-43.6
Kansas, Oklahoma, and Arkan- sas Texas	12 10	12 10		13, 718, 391 12, 132, 707			15, 372, 190 16, 362, 293			22, 375, 075 20, 942, 867		+44.3 +23.3				
Colorado, Montana, Utah, Wyo- ming, and Idaho	8 12 9	8 12 9	3, 954, 582 19, 935, 309 4, 380, 618	23, 350, 674	17.1	4, 024, 563 20, 186, 028 4, 464, 473	28, 019, 494	1.39	23, 787, 808	8, 766, 019 36, 895, 916 12, 003, 754	1.55	+17.8	+4.9 +11.5 +10.4	2 1, 372, 211	935, 077	-31.9
Puerto Rico 8	ĭ	2	462, 628			465, 158							+11.6			+12, 364. 2
	155	155	164, 030, 559	182, 781, 184	+11.4	167, 439, 237	246, 621, 914	1. 47	185, 300, 884	283, 237, 028	1. 53	+10.7	+4.1	<sup>2</sup> 19,964, 918	17, 445, 220	-12.6

Subject to revision.
 Revised figures.
 Includes a new plant in Puerto Rico (September 1942 first month in production).
 Arkansas, Colorado, Florida, Georgia, Idaho, Indiana, Kentucky, Louisiana, Maine, Maryland, Minnesota, Montana, Nebraska, New Jersey, Oklahoma, Oregon, South Dakota, Utah, Virginia, Washington, West Virginia, Wisconsin, and Wyoming.

Production, shipments from mills, and stocks at mills of finished portland cement in the United States in 1942, by months and districts, in thousands of barrels

District	January	February	March	April	May	June	July	August	Septem- ber	October	Novem- ber	Decem- ber
PRODUCTION												
Eastern Pennsylvania, New Jersey, and Maryland New York and Maine Ohio, western Pennsylvania, and West Virginia Michigan Wisconsin, Illinois, Indiana, and Kentucky. Virginia, Tennessee, Alabama, Georgia, Louisiana,	2, 390 850 982 496 1, 265	2, 199 579 852 384 1, 180	*2, 732 748 1, 065 482 1, 229	2, 789 882 1, 134 836 1, 362	2, 783 1, 037 1, 544 1, 068 1, 559	2, 652 1, 173 1, 325 1, 140 1, 627	2, 710 1, 194 1, 309 1, 068 1, 775	2, 792 1, 198 1, 517 968 1, 855	2, 708 1, 177 1, 531 1, 116 1, 882	2, 874 1, 145 1, 831 1, 177 2, 008	2, 567 971 1, 457 1, 061 1, 700	2, 304 739 1, 036 803 1, 214
and Florida  Eastern Missouri, Iowa, Minnesota, and South	1, 687	1, 447	1, 633	1,749	1, 991	1,776	1,868	1, 947	1,942	2, 015	1,937	1,802
Dakota Western Missouri, Nebraska, Kansas, Oklahoma, and Arkansas Texas Colorado, Montana, Utah, Wyoming, and Idaho California Oregon and Washington Puerto Rico <sup>1</sup>	842 777 850 181 1,742 251 47	806 878 113 1,553 279 43	905 976 169 1,656 447 45	791 1,067 949 367 1,590 505 46	1, 003 1, 282 1, 015 407 1, 829 559 42	935 1, 222 1, 045 480 2, 019 584 44	1, 154 1, 235 1, 146 513 2, 180 630 51	1, 506 1, 266 1, 103 476 2, 293 635 49	1, 523 1, 306 1, 036 428 2, 263 576 53	1, 535 1, 385 1, 076 445 2, 186 531 85	1, 367 1, 249 1, 021 392 2, 048 421 83	1, 127 1, 165 1, 043 402 1, 968 436 77
United States: 1942	12, 360 9, 021	10, 797 8, 345	12, 733 10, 596	14, 067 12, 196	16, 119 14, 732	16, 022 15, 223	16, 833 16, 000	17, 605 16, 345	17, 541 16, 115	18, 293 16, 688	16, 274 14, 931	14, 116 13, 810
SHIPMENTS												
Eastern Pennsylvania, New Jersey, and Maryland New York and Maine Ohio, western Pennsylvania, and West Virginia Michigan Wisconsin, Illinois, Indiana, and Kentucky Virginia, Tennessee, Alabama, Georgia, Louisiana, and Florida. Eastern Missouri, Iowa, Minnesota, and South	1, 614 541 590 248 626 1, 442	1, 570 406 533 266 499 1, 245	2,707 649 893 469 975	3, 046 898 1, 246 817 1, 464 2, 013	3, 005 1, 147 1, 385 932 1, 655	3, 089 1, 402 1, 669 1, 033 1, 857	3, 154 1, 418 1, 687 1, 107 2, 279 2, 054	3, 055 1, 349 1, 888 1, 231 2, 687	3, 031 1, 340 2, 022 1, 546 2, 416 2, 162	2, 982 1, 313 2, 388 1, 503 2, 312 2, 150	2, 524 788 1, 246 850 1, 337	1, 294 394 485 340 552 1, 362
Eastern Missouri, Iowa, Minnesota, and South Dakota. Western Missouri, Nebraska, Kansas, Oklahoma, and Arkansas. Texas Colorado, Montana, Utah, Wyoming, and Idaho California Oregon and Washington Puerto Rico 1.	404 765 847 94 1,707	750 811 94 1,488 280	739 1, 142 973 243 1, 635 423	834 1,091 921 338 1,557	946 1,141 1,152 431 2,023 564	1, 276 1, 181 1, 321 595 2, 279 677	1, 775 1, 977 1, 324 718 2, 273 688	2, 446 1, 842 1, 136 552 2, 234 674	1, 835 1, 393 900 472 2, 304 684	1, 845 1, 494 1, 007 434 2, 278 590	1, 163 1, 149 965 377 1, 986 349	326 761 789 240 2,030 304
United States: 1942	9, 115 7, 984	8, 293 7, 456	12, 563 9, 915	14, 774 14, 132	16, 349 16, 048	18, 250 16, 109	20, 501 16, 687	21, 282 17, 825	20, 148 18, 284	20, 384 17, 833	14, 653 13, 724	8, 955 11, 511

STOCKS (END OF MONTH)		-								·		
Eastern Pennsylvania, New Jersey, and Maryland. New York and Maine Ohlo, western Pennsylvania, and West Virginia Michigan Wisconsin, Illinois, Indiana, and Kentucky. Virginia, Tennessee, Alabama, Georgia, Louisiana.	4, 496 2, 156 2, 823 1, 947 2, 242	5, 124 2, 329 3, 141 2, 065 2, 921	5, 150 2, 428 3, 314 2, 077 3, 176	4,893 2,413 3,202 2,097 3,074	4, 671 2, 304 3, 361 2, 233 2, 978	4, 225 2, 075 3, 016 2, 339 2, 747	3, 780 1, 851 2, 637 2, 301 2, 243	3, 516 1, 708 2, 256 2, 038 1, 401	3, 192 1, 545 1, 763 1, 608 871	3, 084 1, 378 1, 206 1, 282 563	3, 126 1, 561 1, 436 1, 492 913	4, 144 1, 914 1, 985 1, 957 1, 574
and Florida  Eastern Missouri, Iowa, Minnesota, and South	1, 349	1, 551	1, 518	1, 255	1, 325	1, 270	1,092	885	665	529	609	1,050
Dakota. Western Missouri, Nebraska, Kansas, Oklahoma,	2,848	3, 025	2, 925	2,870	2, 927	2, 545	1, 936	984	687	377	576	1, 377
western Wissouri, Neoraska, Kansas, Okianoma, and Arkansas.  Texas  Colorado, Montana, Utah, Wyoming, and Idaho California.  Oregon and Washington  Puerto Rico 1	1, 851 742 623 1, 409 678 4	1, 907 809 642 1, 473 677 4	1, 670 811 567 1, 495 701	1, 646 839 595 1, 525 697 6	1,786 702 570 1,336 692	1,828 428 456 1,076 600 4	1, 102 249 250 988 541 9	526 216 175 1,049 503	454 353 131 1,018 400 21	345 422 142 937 341 18	452 478 157 997 413 38	856 732 319 937 545 38
United States: 1942	23, 168 24, 416	25, 668 25, 307	25, 832 25, 988	25, 112 24, 056	24, 886 22, 745	22, 609 21, 865	18, 979 21, 178	15, 268 19, 732	12, 708 17, 561	10, 624 16, 417	12, 248 17, 638	17, 428 19, 925

<sup>&</sup>lt;sup>1</sup> Includes a new plant in Puerto Rico (September 1942 first month in production).

Production and stocks of portland-cement clinker at mills in the United States in 1942, by months and districts, in thousands of barrels

District	January	Febru- ary	March	April	Мау	June	July	August	Septem- ber	October	Novem- ber	Decem- ber
PRODUCTION												
Eastern Pennsylvania, New Jersey, and Maryland. New York and Maine. Ohio, western Pennsylvania, and West Virginia Michigan. Wisconsin, Illinois, Indiana, and Kentucky. Virginia, Tennessee, Alabama, Georgia, Louisiana,	2, 443 880 1, 082 592 1, 321	2, 378 630 877 533 1, 226	2,706 764 1,164 568 1,412	2, 651 895 1, 264 823 1, 269	2,756 1,055 1,368 1,063 1,518	2, 653 1, 169 1, 355 1, 027 1, 586	2, 725 1, 112 1, 304 1, 015 1, 792	2, 800 1, 111 1, 287 922 1, 734	2, 625 1, 139 1, 433 941 1, 817	2, 792 1, 109 1, 636 1, 039 1, 919	2, 628 943 1, 439 1, 017 1, 765	2, 297 733 1, 195 854 1, 381
and Florida  Eastern Missouri, Iowa, Minnesota, and South Da- kota	1, 702 848	1, 624 534	1, 631 635	1, 801 825	1, 929 962	1, 776 914	1, 882 1, 153	1, 917 1, 332	1, 839 1, 415	1, 897 1, 482	1, 893 1, 430	1, 792 1, 227
Western Missouri, Nebraska, Kansas, Oklahoma, and Arkansas Texas Colorado, Montana, Utah, Wyoming, and Idaho California. Oregon and Washington Puerto Rico	851 825 273 1, 668 237 31	786 891 206 1, 572 332 38	936 933 218 1, 964 439 49	1, 019 882 311 1, 869 458 50	1, 226 976 352 1, 921 506 36	1, 172 971 391 1, 964 528	1, 257 1, 131 421 2, 048 607 57	1, 250 1, 100 458 2, 070 539 45	1, 253 1, 027 391 2, 064 591 59	1, 345 1, 054 435 2, 044 502 88	1, 229 1, 033 402 2, 056 437 85	1, 229 1, 068 388 2, 103 425 89
United States: 1942	12, 753 9, 269	11, 627 8, 773	13, 419 11, 325	14, 117 12, 129	15, 668 14, 524	15, 541 14, 964	16, 504 15, 739	16, 565 16, 086	16, 594 15, 668	17, 342 16, 018	16, 357 14, 935	14, 781 14, 197
STOCKS (END OF MONTH)								w-7-0-ii	<del></del>			
Eastern Pennsylvania, New Jersey, and Maryland. New York and Maine. Ohlo, western Pennsylvania, and West Virginia	600 297 695 536 441	782 355 726 685 480	774 378 831 767 661	655 396 965 758 561	644 422 802 747 506	657 427 842 652 458	688 356 851 596 477	706 272 604 550 350	644 244 518 407 284	581 218 327 266 189	650 196 287 219 255	653 197 452 273 416
and Florida. Eastern Missouri, Iowa, Minnesota, and South Da- kota	339 269	517 318	519 346	581 396	527 366	536 336	552 349	527 194	432 111	326 75	286 146	283 250
Western Missouri, Nebraska, Kansas, Oklahoma, and Arkansas Texas Colorado, Montana, Utah, Wyoming, and Idaho California Oregon and Washington Puerto Rico 1	319 232 242 693 351 6	300 256 334 679 405	333 224 384 947 398 9	282 172 329 1, 194 353 14	232 144 276 1, 260 305 10	185 83 188 1, 187 255 3	197 87 98 1,029 238 10	185 97 81 769 149	162 99 45 499 145	130 89 37 354 120 21	124 116 48 346 140 27	192 141 31 447 138 36
United States: 1942	5, 020 5, 092	5, 840 5, 520	6, 571 6, 276	6, 656 6, 207	6, 241 6, 005	5, 809 5, 757	5, 528 5, 522	4, 493 5, 219	3, 601 4, 804	2, 733 4, 192	2, 840 4, 250	3, 509 4, 575

<sup>&</sup>lt;sup>1</sup> Includes a new plant in Puerto Rico (September 1942 first month in production).

End-of-month stocks at mills of both finished portland cement and clinker were relatively stable in the 1935-39 period at average levels of approximately 22½ and 6 million barrels, respectively. However, beginning with 1940, monthly stocks have shown an increasing range of fluctuation in each year through 1942. During January-March 1942 production exceeded shipments, and stocks of finished cement were rebuilt from a relatively low condition at the end of 1941 to 25,832,000 barrels on March 31, or slightly above the customary level. Stocks declined somewhat to the end of May, and then as shipments greatly exceeded production they fell rapidly to a low of 10,624,000 barrels on October 31. The strong demand for cement and the prohibition of assignment of storage space to customers were the principal factors causing this badly depleted condition. A declining demand during November and December enabled producers to replenish stocks approximately halfway to the customary level by the end of 1942. On December 31 stocks of finished cement were 13 percent below those at the end of 1941.

Clinker stocks in 1942 followed essentially the same pattern as stocks of finished cement, except that recovery from the depleted condition at the end of October was less marked. On December 31 stocks were far below the customary level and were 23 percent lower than at the

end of 1941.

Stocks of finished portland cement and portland-cement clinker at mills in the United States on Dec. 31, and yearly range in end-of-month stocks, 1938-42

			Ran	nge	• •	
	Dec. 31 (barrels)	Low		High		
		Month	Barrels	Month	Barrels	
1938 ¹ - {Cement   Clinker   Cement   Clinker   Clinker   Cement   Clinker   Cement   Clinker   Cement   Clinker   Cement   Clinker	4 23, 992, 939 5, 286, 000 23, 645, 583 5, 165, 000 23, 364, 657 4, 886, 000 2 19, 964, 918 4, 575, 000 17, 445, 220 3, 509, 000	October	20, 569, 000 4, 927, 000 19, 870, 000 4, 824, 000 18, 008, 000 4, 470, 000 16, 417, 000 10, 617, 000 2, 723, 000	January	25, 023, 000 6, 732, 000 24, 092, 000 6, 568, 000 26, 118, 000 6, 606, 000 25, 988, 000 25, 832, 000 6, 656, 000	

<sup>&</sup>lt;sup>1</sup> Does not include Puerto Rico, where production began in 1939.

<sup>2</sup> Revised figure.

#### DOMESTIC CONSUMPTION

Consumption of portland cement in States and regions, as indicated by destinations of shipments in 1942, underwent many changes. On a regional basis selected with reference to areas of cement consumption as well as other economic and geographic factors, consumption increased markedly in the Southern and Rocky Mountain States but gained only moderately over 1941 in the Middle and Pacific States. In the Northeastern States consumption declined slightly from 1941.

As shown by figure 2, in which relative rates of gain or loss may be compared readily by slopes of the curves from year to year, consumption of cement declined sharply from the late 1920's to 1933 in all regions except the Rocky Mountain States, where the decline ended in 1932. From these low points there have been irregular general

uptrends in all regions except the Southern States, in which the rising trend has persisted each year. The recovery has been marked in the Southern, Rocky Mountain, and Pacific regions, and it is notable that consumption in these areas in recent years has risen appreciably above the levels attained in the late 1920's. The higher rate and better recovery are attributable to the construction of large power and flood-control dams and, in 1942, to the erection of large war plants and facilities and military establishments in the areas. Consumption of cement in the Northeastern and Middle regions has recovered only moderately from the low points of 1932, and in 1942 the rate was well below the average volumes consumed during 1927–29. States in the regions




FIGURE 2.—Trends of indicated consumption of portland cement in the United States, 1927-42, by regions.

shown on figure 2 are as follows: Northeastern—Connecticut, Delaware, District of Columbia, Maine, Maryland, Massachusetts, New Hampshire, New Jersey, New York, Pennsylvania, Rhode Island, and Vermont; Southern—Alabama, Arkansas, Florida, Georgia, Kentucky, Louisiana, Mississippi, North Carolina, Oklahoma, South Carolina, Tennessee, Texas, Virginia, and West Virginia; Middle—Illinois, Indiana, Iowa, Kansas, Michigan, Minnesota, Missouri, Nebraska, North Dakota, Ohio, South Dakota, and Wisconsin; Rocky Mountain—Arizona, Colorado, Idaho, Montana, Nevada, New Mexico, Utah, and Wyoming; Pacific—California, Oregon, and Washington.

1205

Comparison of indicated cement consumption by States in 1942 and 1941 illustrates the striking effects that location of war construction had on the distribution of consumption. In 1942 consumption increased in 28 States and declined in 20 States and the District of Columbia. The quantities consumed during 1942 in Arkansas, Kansas, Nebraska, Nevada, and South Dakota were more than double the 1941 volumes. Ranking States, in order of consumption, were California, New York, Texas, and Pennsylvania.

The table listing destinations of monthly shipments of portland cement was compiled from the regular monthly reports of producers.

Destination of shipments of finished portland cement from mills in the United States, 1940-42, by States

		,	19	42
Destination	1940 (barrels)	1941 (barrels)	Barrels	Percent of change from 1941
Alabama	1, 458, 811	2, 491, 851	3, 237, 883	+29.9
Arizona <sup>1</sup>	558, 629	793, 838	1, 379, 825	+73.8
Arkansas	812, 931	1, 146, 712	2, 931, 890	+155.7
California	11; 619, 397	16, 850, 718	17, 444, 451	+3. 8
Colorado	1, 028, 753	1, 520, 646	2, 204, 461	+45. (
Connecticut 1	1, 893, 733	2, 379, 471	1, 996, 198	<b>—16.</b> 1
Delaware 1	416, 056	394, 451	348, 283	-11.
District of Columbia 1	1, 605, 768	1, 590, 499	1, 566, 360	-1. 8
Florida	2, 442, 623	3, 172, 179	3, 640, 849	+14.8
Georgia	1, 901, 663	2, 671, 255	2, 991, 447	+12.0
[daho	334, 360	448, 380	570, 378	+27. 2
llinois	8, 584, 009	9, 165, 894	9, 717, 134 6, 359, 018	+6.0 +19.
ndiana	3, 628, 891	5, 319, 791	2, 317, 264	+19. 8 -28. 9
owa	2, 933, 570 1, 627, 535	3, 259, 370 2, 061, 704	4, 704, 821	+128.2
Kansas	2, 006, 097	2, 705, 374	2, 613, 180	T120. 4
Kentucky	2, 168, 927	2, 837, 225	3, 327, 152	+17.
Louisiana	331, 685	623, 245	559, 731	-10.
Maine Maryland	2, 141, 788	3, 093, 522	3, 036, 945	-1.8
Massachusetts 1	2, 707, 242	3, 029, 370	2, 715, 651	-10.
Michigan	5, 760, 481	6, 907, 824	7, 069, 832	+2.
Minnesota	2, 562, 578	3, 035, 480	2, 320, 780	-23.
Mississippi <sup>1</sup>	1, 330, 367	1, 407, 063	1, 467, 849	+4.
Missouri	3, 150, 489	5, 029, 976	3, 877, 208	-22.9
Montana	419, 796	457, 899	483, 139	+5.
Nebraska	1, 122, 140	1, 380, 339	4, 519, 493	+227.
Vevada 1	172, 710	250, 236	1, 551, 797	+520.
New Hampshire 1	428, 752	518, 691	456, 845	-11.
New Jersey	4, 165, 289	5, 353, 149	5, 149, 525	-3.
New Mexico 1	514, 490	749, 023	696, 841	-7. -13.
New York	13, 119, 568	14, 096, 501	12, 139, 320 2, 420, 086	-13. -6.
North Carolina 1	1,770,738	2, 574, 455 361, 416	291, 977	-19.
North Dakota 1	290, 711 6, 538, 166	8, 455, 877	8, 160, 031	-3.
Ohio	1, 886, 668	2, 131, 784	3, 218, 926	+51.
Oklahoma	906, 358	1, 529, 971	1, 350, 988	-11.
OregonPennsylvania	10, 008, 425	10, 000, 181	10, 157, 308	+1.
Rhode Island 1	649, 373	834, 261	963, 073	+15.
South Carolina 1	1, 118, 340	1, 759, 468	1, 927, 768	+9.
South Dakota	427, 254	432, 431	1, 055, 170	+144.
rennessee	2, 455, 317	4, 281, 918	5, 282, 485	<b>+23.</b>
Гехаs	6, 478, 976	8, 598, 148	11, 401, 189	+32.
Utah	679, 370	1, 196, 451	1, 997, 820	+67.
Vermont 1	246, 820	238, 436	126, 412	-47.
Virginia	2, 381, 902	4, 771, 954	6, 435, 358	+34.
Washington	3, 540, 956	3, 015, 298	4, 266, 440	+41. -12.
West Virginia	1, 318, 364	1,690,142	1, 481, 319 3, 056, 916	-12. -4.
Wisconsin Wyoming	2, 604, 168 250, 901	3, 187, 293 284, 771	378, 704	+33.
	126, 501, 935	160, 085, 931	177, 367, 520	+10.
Unspecified 2	3, 847, 851	7, 353, 306	7, 933, 364	+7.
Total shipped from cement plants	130, 349, 786	167, 439, 237	185, 300, 884	+10.

Non-cement-producing State.
 Includes shipments to Alaska, Hawaii, Puerto Rico, and foreign countries.

# Destination of shipments of finished portland cement from mills in the United States in 1942, by months, in barrels

·										19.00		
Destination	January	February	March	April	May	June	July	August	September	October	November	December
Alabama	261, 888	258, 003	309, 777	385, 674	272, 114	230, 181	000 400	040.004	040 407	200 504	4-1-2-	
Arizona		54, 467	61, 688	58, 370	84,708		288, 400	249, 224	242, 485	292, 534	274, 739	172, 301
Arkansas	166, 559	163, 096	194, 386	170, 318		132, 695	164, 661	176, 093	166, 289	160, 058	152, 334	129, 928
California	1, 448, 286	1, 127, 592	1, 274, 509		149, 269	215, 874	339, 062	391, 075	451, 260	335, 284	215, 165	139, 238
Colorado	42, 393			1, 166, 352	1, 177, 312	1, 647, 084	1, 697, 570	1, 539, 703	1, 629, 143	1, 649, 885	1, 376, 030	1, 419, 739
Connections	42, 393	31, 994	116, 184	164, 750	514, 680	284, 405	432, 165	414, 023	198, 545	128, 260	117, 020	54, 518
Connecticut	72,071	63, 071	120, 552	188, 815	219,050	223, 432	236, 320	218, 295	186, 956	225, 222	155, 934	55, 973
Delaware District of Columbia	13, 368	8, 475	22, 555	27, 396	26, 924	50,605	42, 281	33, 627	31, 254	38, 194	32, 541	14, 258
District of Columbia	111,094	107, 875	140,004	156, 913	148, 735	130, 385	136, 483	134, 513	150, 716	120, 652	126, 023	81, 531
Florida	219, 043	210, 681	200, 369	266, 376	267, 482	240,777	348, 520	425, 323	421, 082	449, 963	338, 225	251, 481
Georgia	217, 904	172, 222	215, 729	262, 722	247, 258	250, 783	297, 382	285, 519	251, 567	311, 804	277, 210	200, 240
Idaho	8,021	15, 154	31, 421	39, 126	33, 290	60, 969	80, 308	65, 990	54, 952	57, 067	39, 561	15, 583
Illinois	324, 494	273, 253	546, 633	731, 065	748, 489	864, 042	1,092,098	1, 368, 640	1, 204, 326	1, 232, 749	624, 236	305, 945
Indiana		147, 386	300, 659	437, 103	537, 898	579, 982	712, 805	918, 345	1, 026, 031	986, 339	422, 513	126, 015
Iowa		40, 339	135, 078	210, 888	250, 116	304, 466	361, 692	485, 851	341, 634	374, 574	158, 927	
Kansas	133, 607	139, 083	238, 150	251, 935	287, 789	309, 486	551, 457	591, 147	653, 428	842, 296		23, 872
Kentucky	116, 787	101, 572	135, 127	190, 223	272, 089	371, 979	355, 781	338, 649	327, 075	243, 640	485, 041	207, 389
Kentucky Louisiana	249, 919	200, 793	322, 061	319, 064	293, 379	246, 088	302, 159	318, 448	342, 899		116, 524	42, 462
Maine	21 222	23, 092	24, 725	31, 011	42, 626	53, 388	70, 501	318, 448		267, 919	245, 075	217, 983
Maryland	156, 843	134, 965	222, 266	270, 115	300, 302	306, 412		87, 697	59, 812	70, 989	37, 093	20, 340
Massachusetts	134, 161	121, 245	201, 578	251, 959	295, 035		311, 597	307, 455	322, 619	274, 727	256, 705	166, 458
Maryland Massachusetts Michigan	177, 648	190, 478	348, 795	598, 752		317, 958	296, 285	283, 326	295, 614	290, 546	167, 990	84, 900
Minnesota	47, 458	51, 082	157, 293	203, 604	688, 310	693, 911	680, 017	814, 901	1,044,500	989, 892	631, 501	269, 823
Mississippi	136, 086	64, 719			234, 130	285, 830	296, 035	368, 331	260, 116	278, 165	90, 175	28, 613
Missouri	263, 082		73, 434	91, 378	87, 687	123, 091	172, 038	154, 473	147, 838	186, 950	142, 110	88, 101
Montana	11 054	166, 664	357, 662	341, 089	325, 692	280, 144	389, 566	588, 029	354, 253	420, 642	253, 795	134, 373
Mohradra	11,054	7,997	16, 813	25, 887	40, 562	52, 086	107, 508	113, 542	50,648	30, 959	17, 765	8,072
Nebraska	26, 624	27, 329	64, 836	172, 814	165, 779	210, 282	457, 221	608, 921	544, 659	1, 182, 543	887, 665	130, 566
Nevada	55, 464	70,609	91,054	92,041	97, 999	96, 184	119, 876	160, 118	182, 839	204, 893	176, 133	204, 183
New Hampshire	20, 396	18, 851	28, 720	35, 891	46, 888	56, 765	47, 841	52, 339	50, 790	64, 748	29, 336	16, 099
New Jersey	. 330, 303	259, 598	494, 459	459, 736	438, 493	489, 751	648, 240	531, 622	516, 216	492, 758	360, 128	216, 049
New Mexico	36, 601	32,714	49, 591	101, 834	64, 250	47, 456	102, 439	82, 604	65, 429	46, 606	24, 695	41, 531
New York	541, 952	446, 775	740, 214	1,027,596	1, 249, 721	1,500,903	1, 435, 146	1, 444, 380	1, 281, 642	1, 233, 610	781, 039	358, 089
North Carolina	150, 714	119,666	169, 353	215, 684	208, 337	221, 979	260, 654	255, 674	260, 557	249, 724	185, 111	120, 391
NORIII Dakota	4,754	8,574	25, 262	13, 169	23, 739	62, 062	61, 895	49, 929	16, 211	19, 356	5, 602	1 070
Ohio	296, 020	265, 250	501, 024	693, 350	792, 994	933, 765	917, 393	1, 022, 606	1, 033, 482	907, 394	547, 655	1, 276
Oklahoma	216, 730	186,720	342, 260	204, 590	286, 807	225, 585	306, 577	227, 814	234, 780			247, 702
Oregon	39,076	58, 078	108, 519	161, 274	173, 491	169, 226	154, 491	135, 149	204, 780	345, 880	349, 048	287, 926
Oregon Pennsylvania Rhode Island	429, 359	397, 481	705, 291	889, 937	921, 836	1, 108, 027			133, 553	111,605	49, 951	50, 826
Rhode Island	29, 612	25, 432	49, 172	75, 164	101, 389	116, 909	1, 171, 598	1, 185, 671	1, 188, 404	1, 010, 939	742, 270	374, 834
South Carolina South Dakota	95, 811	68, 300	102, 488	116, 909	176, 784	222, 460	131, 790	108, 361	114, 227	119, 440	88, 364	36, 379
South Dakota	12, 215	9, 315	39, 017	35, 165	53, 833		157, 815	148, 714	125, 216	198, 710	270, 204	243, 993
Tennessee	207, 137	156, 545	318, 541	357, 297	462, 071	165, 618	251, 277	198, 861	168, 646	93, 744	22, 412	4, 766
Texas	802, 429	774, 183	962, 925		1 000 717	433, 946	480, 658.	505, 792	589, 404	695, 263	699, 340	359, 413
Utah	14, 951	21, 328	49, 180	749, 199	1,029,717	1, 253, 896	1, 434, 997	1, 288, 220	879, 917	815, 148	767, 016	643, 483
Vermont	3, 220	1, 687		66, 954	87, 296	152, 389	199, 937	336, 651	355, 045	295, 550	248, 402	169, 475
Virginia	329, 043	395, 665	8, 337	11,808	13, 270	16, 847	16, 587	15, 145	16, 802	16, 216	5, 420	2, 929
P	1 040,040	000,000	568, 507	688, 159	730, 881	640, 012	670, 939	589, 033	628, 876	482, 797	495, 087	234, 773

Washington West Virginia Wisconsin Wyoming	159, 386	218, 396	307, 126	341, 720	383, 780	500, 847	510, 057	518, 586	541, 276	460, 716	304, 716	247, 303
	70, 616	63, 092	102, 574	142, 748	135, 551	187, 669	176, 278	157, 831	137, 711	144, 655	108, 757	55, 165
	71, 220	77, 722	174, 987	270, 041	286, 877	395, 273	451, 091	429, 111	361, 021	346, 544	145, 059	46, 908
	6, 689	5, 959	8, 880	15, 445	18, 779	47, 150	103, 298	89, 804	17, 403	32, 558	20, 096	8, 019
Unspecified 1	8, 536, 853	7, 584, 567	11, 779, 765	13, 779, 410	15, 495, 488	17, 511, 054	20, 030, 786	20, 815, 155	19, 659, 148	19, 830, 707	14, 067, 738	8, 361, 214
	578, 147	708, 433	783, 235	994, 590	853, 512	738, 946	470, 214	466, 845	488, 852	553, 293	585, 262	593, 786
Total shipped from cement plants	9, 115, 000	8, 293, 000	12, 563, 000	14, 774, 000	16, 349, 000	18, 250, 000	20, 501, 000	21, 282, 000	20, 148, 000	20, 384, 000	14, 653, 000	8, 955, 000

Includes shipments to Alaska, Hawaii, Puerto Rico, and foreign countries.

#### LOCAL SUPPLIES

Of the 35 producing States in 1942, more portland cement was produced than consumed internally in 17 and production was less than requirements within the State in 18. Puerto Rico consumed more cement than was produced. Owing to the large aggregate capacity of mills in the State, the greatest surplus was recorded for Pennsylvania. These data, however, do not show areas or States in which a definite shortage of cement existed, because parts of any State commonly are supplied from mills of a neighboring State.

The total surplus of the producing States was distributed as follows: In 1941—to non-cement-producing States, 16,880,678 barrels, and to foreign countries, Alaska, Hawaii, and unspecified destinations, 5,919,919 barrels; in 1942—to non-cement-producing States, 17,908,965 barrels, and to foreign countries, Alaska, Hawaii, and unspecified destinations, 6,930,952 barrels.

Estimated surplus or deficiency in local supply of portland cement in cement-producing States, 1941-42, in barrels

		1941			1942	
State or division	Shipments from mills	Estimated consump- tion	Surplus or deficiency	Shipments from mills	Estimated consumption	Surplus or deficiency
Alabama California Illimois Ilowa Kansas Michigan Missouri Ohio Pennsylvania PuertoRico Tennessee Texas Colorado, Montana, Utah, Wyoming, and Idaho Oregon and Washington Georgia, Kentucky, Virginia, Florida, and Louisiana Indiana, Wisconsin, Minnesota, Nebraska, Oklahoma, South Dakota, and Arkansas Maryland, New Jersey, and West Virginia New York and Maine	20, 186, 028 5, 958, 376 5, 328, 398 4, 734, 129 9, 819, 218 6, 516, 345 8, 021, 857 32, 888, 220 455, 158 5, 623, 800 9, 842, 260 4, 024, 563 4, 464, 473 8, 493, 161 15, 500, 432 5, 932, 957 12, 049, 832	16, 850, 718 9, 165, 894 3, 259, 370 2, 061, 704 6, 907, 824 5, 029, 976 8, 455, 877 10, 000, 181 1, 433, 387 4, 281, 918 8, 598, 148 3, 908, 147 4, 545, 269 16, 157, 987 16, 633, 830 10, 136, 813 14, 719, 746	+3, 335, 310 -3, 207, 518 +2, 069, 028 +2, 672, 425 +2, 911, 335 +1, 486, 369 -434, 020 -22, 868, 039 -968, 229 +1, 341, 882 +1, 244, 112 +116, 416 -80, 796 -7, 664, 826 -1, 133, 398 -4, 203, 856 -2, 669, 914	23, 787, 808 7, 102, 393 5, 662, 733 7, 726, 291 10, 349, 104 7, 397, 960 8, 652, 196 33, 639, 025 6, 407, 196 12, 139, 800 4, 588, 428 5, 940, 938 8, 074, 555 18, 137, 387 4, 822, 553 11, 644, 827	17, 444, 451 9, 717, 134 2, 317, 264 4, 704, 821 7, 069, 832 3, 877, 208 8, 160, 031 10, 157, 308 1, 002, 412 5, 282, 485 11, 401, 189 5, 634, 502 5, 617, 428 19, 007, 986 23, 462, 193 9, 667, 789 12, 699, 051	+6, 343, 35' -2, 614, 74' +3, 345, 46' +3, 021, 47' +3, 279, 27' +3, 520, 75' +492, 161' +23, 481, 71' -373, 05' +1, 124, 71' +738, 61' -1, 046, 07' +323, 51( -10, 933, 431' -5, 324, 806' -4, 845, 236' -1, 054, 224'
	167, 439, 237	144, 638, 640	+22, 800, 597	185, 300, 884	160, 460, 967	+24, 839, 917

#### TRANSPORTATION

Methods and means of shipping portland cement from producing mills have changed considerably in recent years. Because of conditions imposed by the war, the changes from 1941 to 1942 probably were more marked than those between any other successive years. As shown in figure 3, there was a growing use of truck haulage from 1934, the first year for which data are available, to 1941. However, in 1942, the percentage hauled by truck decreased from 1941, owing undoubtedly to war restrictions on tires and gasoline. Rail shipments, which represent by far the major part of total cement movements, showed a small decrease in percentage from 1934 to 1941

but in 1942 regained most of the loss and returned nearly to 1934 proportions. Shipments by boat constitute only a small part of the total and have declined in percentage from 1934.




FIGURE 3.—Percentage distribution of portland-cement shipments from mills in 1934, 1941, and 1942, by types of carriers and by bulk and types of containers.

Distribution of cement shipments by bulk and types of containers in 1942 from 1941 differed considerably and differed also from the practice in 1934 and 1928. In 1928, only 2.4 percent of total shipments were made in bulk, and the rest were made in containers. Cloth bags apparently were the most popular containers used in 1928, although no specific data are available. After 1928 the proportions of bulk shipments increased rapidly to 20 percent in 1934 and 31 percent in 1941. Owing to the scarcity of packaging materials and to the fact that much of the construction in 1942 comprised large projects requiring much cement, the proportion of bulk shipments jumped to 42 percent of the total in 1942. Although the percentage of total shipments in cloth bags in 1934 was slightly higher than that in paper bags, by 1941 paper-bag shipments represented 40 percent of the total, compared with only 29 percent in cloth. As a result of the paper shortage in 1942 and the greater demand for bulk cement, the proportion shipped in paper declined to less than one-third of the total and was only slightly greater than the percentage shipped in cloth. The proportion shipped in cloth declined only slightly from 1941.

Shipments of portland cement from mills in the United States, 1940-42, in bulk and in containers, by types of carriers

[Barrels of 376 pounds]

				In cont	ainers			
Type of carrier	In bt	ılk	В	ags	Other		Total ship	ments
			Paper	Cloth	contain- ers <sup>1</sup>	Total		
1940 <sup>2</sup> Truck Railroad Boat	Barrels 3 3, 873, 113 28, 870, 110 614, 471	Percent 11. 6 86. 5 1. 9	Barrels 8, 325, 992 45, 724, 386 1, 319, 683	Barrels 8, 095, 980 32, 522, 949 971, 870	Barrels 23, 527	Barrels 16, 421, 972 78, 270, 862	Barrels 20, 295, 085 107, 140, 972	Per- cent 15. 6 82. 2
Pipe line Percent of total	7, 705 33, 365, 399 25. 6	100.0	55, 370, 061 42. 5	41, 590, 799	23, 527	2, 291, 553  96, 984, 387 74, 4	2, 906, 024 7, 705 130, 349, 786 100. 0	2. 2 (4)
Truck Railroad Boat Pipe line	\$ 5, 481, 732 44, 641, 936 1, 559, 678 142, 365	10. 6 86. 1 3. 0	9, 989, 551 53, 863, 493 2, 414, 842	9, 310, 998 39, 506, 899 496, 452	31, 141 150	19, 300, 549 93, 401, 533 2, 911, 444	24, 782, 281 138, 043, 469 4, 471, 122 142, 365	14. 8 82. 4 2. 7
Percent of total 1942 <sup>2</sup>	51, 825, 711 31. 0	100.0	66, 267, 886	49, 314, 349 29. 4	31, 291 (4)	115, 613, 526 69. 0	167, 439, 237 100. 0	100.0
Truck Railroad Boat	\$ 8, 925, 440 66, 764, 363 2, 097, 849	11. 5 85. 8 2. 7	8, 206, 616 49, 385, 586 690, 341	6, 306, 601 42, 440, 744 474, 678	8,666	14, 513, 217 91, 834, 996 1, 165, 019	23, 438, 657 158, 599, 359 3, 262, 868	12. 6 85. 6 1. 8
Percent of total	77, 787, 652 42. 0	100.0	58, 282, 543 31. 4	49, 222, 023 26. 6	8, 666 (4)	107, 513, <b>2</b> 32 58. 0	185, 300, 884 100. 0	100.0

Includes steel drums and iron and wood barrels.

### PRICES

Reflecting increased costs of production, the average selling value of all portland cement at the mill, excluding cost of containers and cash discounts, advanced 6 cents over 1941 to \$1.53 per barrel in 1942. This average value, as computed from reported data, is higher than an average value for general-purpose cement because it includes special cements with relatively high prices.

Average mill value per barrel, in bul	k, of po	rtland cement in the United States, 193	8-42
1938 <sup>1</sup> 1939 1940		1941\$   1942\$	1. 47 1. 53

<sup>1</sup> Does not include Puerto Rico, where production began in 1939.

A study 1 of wholesale and retail prices of building materials states that portland cement generally is sold under the multiple basing-point price system, in which basing points are usually producing centers. average wholesale and retail prices of portland cement in September 1939 in the 26 cities surveyed was \$2.01 and \$2.67 per barrel, respectively, an average spread of 33 percent. In general, the highest prices were reported in the West South Central and Rocky Mountain States, and the lowest were in the East North Central area. Both wholesale and retail prices showed fairly wide geographical variations.

Includes shipments for Puerto Rico.

Includes cement used at mills by producers as follows—1940: 118,709 barrels; 1941: 196,765 barrels; 1942: 181,642 barrels.

4 Less than 0.05 percent.

<sup>&</sup>lt;sup>1</sup> Temporary National Economic Committee ,Geographical Differentials in Prices of Building Materials. Mono. 33, 1940, pp. 89–103.

#### CAPACITY OF PLANTS

Aggregate capacity of all portland cement plants increased slightly over 1941 and was utilized at 73.5 percent of the total to produce the record output in 1942. Capacity data for 1942 include 155 active plants and 1 inactive plant that produced or shipped since the beginning of 1935. Figures for 1 plant each in Indiana and New Jersey that ceased operations and were dismantled in 1942 also are included. The data were compiled from reports of producers, who were asked to make allowances for repairs and other unavoidable shut-downs, and are expressed in terms of finished portland cement so as to cover the limiting factor in production at each mill, whether it be in the rawgrinding, burning, or finish-grinding departments. During 1942, operators in the Texas, Virginia-Tennessee-Alabama-Georgia-Florida-Louisiana, California, and Puerto Rico districts used the largest percentage of installed capacity.

Portland-cement-manufacturing capacity of the United States, 1941-42, by producing districts

District	Estimate (bar	Percent of capacity utilized		
	1941	1942	1941	1942
Eastern Pennsylvania, New Jersey, and Maryland	45, 274, 000 17, 244, 000 26, 574, 000 28, 267, 000 28, 267, 000 24, 512, 000 16, 598, 000 5, 815, 000 5, 815, 000 463, 000 247, 359, 000	45, 554, 000 17, 626, 000 26, 243, 000 28, 623, 000 28, 662, 000 24, 612, 870 20, 936, 622 16, 915, 000 27, 071, 302 7, 440, 000 248, 850, 948	68. 5 69. 6 57. 0 67. 5 57. 4 81. 5 52. 8 59. 7 78. 4 68. 0 75. 8 99. 9	69. 2 66. 4 59. 3 75. 5 65. 0 88. 6 61. 3 81. 1 91. 9 73. 8 86. 3 78. 8 109. 3

<sup>1</sup> Includes a new plant in Puerto Rico (September 1942 first month in production).

It is noteworthy that of the 155 plants active in 1942, 83, or 54 percent of the total, had an installed annual capacity between 1,000,000 and 1,999,000 barrels.

Distribution of portland-cement plants in the United States in 1942, according to annual capacity

Capacity Capacity	Number
Estimated annual capacity, barrels:	of plants
Less than 1,000,000	37
1,000,000 to 1,999,000	83
2,000,000 to 2,999,000	
Between 2,999,000 and 10,000,000	
	1 = 0

Percentage of capacity used in each month of 1942 was well above that for the corresponding month of 1941. In 1942 the monthly percentage utilized increased steadily from the low of 57 in February to the high of 87 in September and October, from which it fell to 67 in December.

Percent of capacity used in the finished portland-cement industry in the United States, 1941–42 ·

Month	Month	nly	12 mo ende		Monthly		Monthly		onths ed—
JanuaryFebruaryMarchAprilMayJune	1941 1 42 43 50 59 69 74	59 57 61 69 77 79	53 54 56 57 57 57	67 69 69 70 71 71	July	75 77 78 79 73 65	80 85 87 87 87 80 67	1941 60 61 62 64 65 65	71 73 73 73 73 74 74

Capacity of portland-cement plants in the United States, 1940-42, by processes

Process			Capacity	7	Perc	ent of c	eanac-	Per	Percent of total				
Process	Thou	sands of b	arrels	Per	Percent of total			ity utilized			finished cement produced		
	1940	1941	1942	1940	1941	1942	1940	1941	1942	1940	1941	1942	
Wet Dry	122, 266 131, 879	121, 065 126, 294	122, 432 126, 419	48. 1 51. 9	48.9 51.1	49. 2 50. 8	55. 4 47. 4	70.3 62.5	77. 7 69. 3	52. 0 48. 0	51. 9 48. 1	52. 1 47. 9	
	254, 145	247, 359	248, 851	100. 0	100.0	100.0	51. 2	66.3	73. 5	100.0	100.0	100.0	

Although in recent years the aggregate capacity of dry-process plants was slightly greater than that of wet-process plants, it seems significant that in recent years the wet-process capacity has been utilized more fully than the dry-process capacity.

## CLINKER PRODUCTION

Production of clinker, the intermediate product of the industry, gained 11 percent over 1941. Stocks at mills on December 31, 1942, were unusually low and were 23 percent below those at the end of 1941.

Portland-cement clinker produced and in stock at mills in the United States, 1941-42, by processes, in barrels of 376 pounds 1

Process	Pla	nts	Produ	etion	Stock (Dec. 31)		
Frocess	1941	1942	1941	1942	1941 2	1942 3	
Wet	90 65	90 65	84, 568, 000 79, 061, 000	93, 817, 195 87, 450, 266	2, 499, 495 2, 075, 033	1, 722, 266 1, 787, 070	
	155	155	163, 629, 000	181, 267, 461	4, 574, 528	3, 509, 33	

<sup>1</sup> Compiled from monthly estimates of the producers.

# PRODUCTION ACCORDING TO RAW MATERIALS

The relationship of the percentages of total output classified according to kinds of raw materials changed little in 1942 from 1941.

As indicated by the data available, mills employing cement rock and limestone have furnished approximately the same proportion of total output each year since 1912. However, in the 1900-1912

<sup>2</sup> Revised figures.
3 Subject to revision.

**CEMENT** 1213

period there was a steady decline in the annual percentages supplied from these mills, which are mainly in eastern Pennsylvania and New Jersey. The decline was caused by the gradual spreading of the industry into all sections of the country and the concomitant erection of new plants using limestone and clay or shale as raw materials. Mills employing the latter group of raw materials supplied a generally rising percentage of total production until about 1926, from which, up to the present time, the annual proportion has fluctuated in a relatively narrow range. Since 1899, the proportion of total output of cement derived from marl and clay has declined more or less regularly to the present low percentages. Cements derived from slag and limestone have represented a relatively small and declining part of total production in recent years.

Production and percent of total output of portland cement in the United States, 1898-1914, 1926, 1929, 1933, 1935, 1941, and 1942, according to raw materials

Year	Cement rock and pure limestone		Limestone and clay or shale		Marl and clay		Blast-furnace slag and limestone	
	Barrels	Per- cent	Barrels	Per- cent	Barrels	Per- cent	Barrels	Per- cent
898		74. 9	365, 408	9. 9	562,092	15. 2		
899	4, 010, 132	70.9	546, 200	9.7	1, 095, 934	19.4		
900	5, 960, 739	70.3	1,034,041	12.2	1,454,797	17.1	32,443	0.4 1.3
901	8,503,500	66. 9	2,042,209	16. 1 21. 7	2, 001, 200 2, 220, 453	15.7 12.9	164, 316 318, 710	1.8
902	10, 953, 178	63. 6 55. 9	3, 738, 303 6, 333, 403	28.3	3, 052, 946	13.7	462, 930	2.
903	12, 493, 694 15, 173, 391	57. 2	7, 526, 323	28.4	3, 332, 873	12.6	473, 294	1.
905	18, 454, 902	52.4	11, 172, 389	31.7	3, 884, 178	11.0	1, 735, 343	4.
906	23, 896, 951	51.4	16, 532, 212	35. 6	3,958,201	8.5	2,076,000	4.
907	25, 859, 095	53. 0	17, 190, 697	35. 2	3,606,598	7.4	2, 129, 000	4.
908	20, 678, 693	40.6	23, 047, 707	45.0	2, 811, 212	5. 5	4, 535, 300	8.
909	24, 274, 047	37.3	32, 219, 365	49.6	2, 711, 219	4.2	5, 786, 800	8.
910	26, 520, 911	34.6	39, 720, 320	51.9	3, 307, 220	4.3	7, 001, 500	9.
911	26, 812, 129	34.1	40, 665, 332	51.8	3, 314, 176	4.2	7, 737, 000	9.
912		30.0	44, 607, 776	54.1	2, 467, 368	3.0	10,650,172	12.
913	29, 333, 490	31.8	47, 831, 863	51.9	3, 734, 778	4.1	11, 197, 000	12. 10.
914	24, 907, 047	28.2	50, 168, 813	56.9	4, 038, 310	4.6	9, 116, 000	9.
926	44,090,657	26.8	1 101, 637, 866	61.8	3, 324, 408 4, 832, 700	2.0 2.9	15, 477, 239 17, 112, 800	10.
929 933		29. 9 22. 3	1 97, 623, 502 1 43, 638, 023	57. 2 68. 7	1, 402, 744	2. 9	4, 297, 251	6.
935 935		31.0	1 45, 073, 144	58.8	1, 478, 569	1.9	6, 378, 170	8.
935 941	23, 811, 687 46, 534, 193	28.4	1 102, 285, 699	62.3	3, 142, 021	1.9	12,068,646	7.
942	49, 479, 304	27.0	1 115, 948, 373	63.4	3, 009, 562	1.7	14, 343, 945	7.

<sup>&</sup>lt;sup>1</sup> Includes output of 2 plants using oystershells and clay in 1926; 3 plants in 1929, 1933, and 1935; and 4 plants in 1941 and 1942.

#### RAW MATERIALS

Approximately 58,853,443 short tons of raw materials (exclusive of fuels and explosives) entered into the manufacture of 182,781,184 barrels (34,362,863 short tons) of portland cement in 1942, an average of 644 pounds to a 376-pound barrel of finished cement. The totals for 1942, with corresponding figures for 1941 (in parentheses), follow: 47,657,208 tons of limestone and cement rock (42,733,707 tons); 5,181,582 tons of clay and shale (4,726,192 tons); 809,371 tons of slag (659,201 tons); 903,360 tons of marl (1,066,635 tons); 1,248,448 tons of gypsum (1,035,179 tons); and 3,053,474 tons of other materials such as oyster shells, sandstone, sand, cinders, fluorspar, iron ore, diatomaceous shale, pumicite, fuller's earth, bentonite, silica, quartz, ashes, pyrite cinder and ore, roll scale, calcium chloride, and hydrated lime (2,534,339 tons).

### FUELS AND POWER

Fuels.—The fuel-oil shortage in the Eastern States in the latter half of 1942 forced cement plants to convert from oil to coal wherever As a result, and because of increased production, the quantity of coal consumed by the portland-cement industry increased markedly over 1941. However, total consumption of fuel oil declined only slightly owing to the greater output of cement in areas where oil was not restricted. Consumption of natural gas by the industry was well above 1941. At the end of 1942, greatly increased requirements for natural gas for industrial and heating purposes caused local shortages in Kansas and Nebraska, and mills in that area had difficulty in obtaining adequate supplies.

Finished portland cement produced and fuel consumed by the portland-cement industry in the United States, 1941-42, by processes

	Finished cement produced			Fuel consumed 1			
Process	Plants	Barrels of 376 pounds	Percent of total	Coal (short tons)	Oil (barrels of 42 gal- lons)	Natural gas (cubic feet)	
Wet Dry	90 65	85, 153, 919 78, 876, 640	51. 9 48. 1	<sup>2</sup> 3, 325, 823 3, 506, 002	2, 090, 700 1, 461, 330	34, 045, 968, 833 20, 161, 932, 000	
선생님 보는 사람들이 되었다.	155	164, 030, 559	100.0	3 6, 831, 825	3, 552, 030	54, 207, 900, 833	
Wet Dry	90 65 155	95, 171, 022 87, 610, 162 182, 781, 184	52. 1 47. 9 100. 0	4 3, 637, 571 3, 932, 516 5 7, 570, 087	1, 896, 044 1, 532, 975 3, 429, 019	40, 850, 105, 348 23, 689, 722, 940 64, 539, 828, 288	

Figures compiled from monthly estimates of the producers.
 In addition to the coal shown for this group, 2 plants reported the use of petroleum coke with coal and

<sup>3</sup> Includes 96,768 short tons of anthracite and 6,735,057 short tons of bituminous coal.

<sup>4</sup> In addition to the coal shown for this group, 1 plant reported the use of petroleum coke with coal and

<sup>5</sup> Includes 107,653 short tons of anthracite and 7,462,434 short tons of bituminous coal.

Finished portland cement produced and fuel consumed by the portland-cement industry in the United States, 1941-42, by kinds of fuel

	Finished cement produced			Fuel consumed 1			
Fuel	Plants	Barrels of 376 pounds	Percent of total	Coal(short tons)	Oil (barrels of 42 gal- lons)	Natural gas (cubic feet)	
1941 Coal	102 11 15 6 15 5	2 104, 385, 531 2 11, 341, 543 2 14, 933, 181 9, 501, 559 13, 454, 345 } 10, 414, 400	63. 6 7. 0 9. 1 5. 8 8. 2 6. 3	6, 193, 207 508, 571 128, 659 {	2, 524, 587 567, 318 422, 223 37, 902	22, 127, 284, 511 19, 666, 186, 322 11, 073, 254, 000 1, 341, 176, 000	
	155	164, 030, 559	100.0	4 6, 831, 825	3, 552, 030	54, 207, 900, 833	
1942 CoalOilNatural gas	98 12 12	<sup>2</sup> 107, 168, 837 <sup>2</sup> 12, 893, 278 <sup>2</sup> 15, 103, 415	58. 6 7. 0 8. 3	6, 329, 228	2, 820, 520	21, 641, 045, 940	

 Figures compiled from monthly estimates of the producers.
 Average consumption of fuel per barrel of cement produced was as follows: 1941—coal, 118.7 pounds;
 oil, 0.2226 barrel; natural gas, 1,482 cubic feet. 1942—coal, 118.1 pounds;
 oil, 0.2188 barrel; natural gas, 1.433 cubic feet

<sup>3</sup> In addition to the coal and natural gas included for this group, 2 plants reported the use of petroleum coke with coal and natural gas.

Includes 96,768 short tons of anthracite and 6,735,057 short tons of bituminous coal.

できることできるというと、またのではないのでは、これのでは、これでは、これできることできることできるとのできるというできるというできるというできるというできるというできるというできるというできるという

Finished portland cement produced and fuel consumed by the portland-cement industry in the United States, 1941-42, by kinds of fuel—Continued

	Finished cement produced			Fuel consumed <sup>1</sup>			
Fuel	Plants	Barrels of 376 pounds	Percent of total	Coal (short tons)	Oil (barrels of 42 gal- lons)	Natural gas (cubic feet)	
1942—Continued Coal and oil	9 13 7 4	14, 938, 889 14, 443, 714 13, 269, 603 4, 963, 448	8. 2 7. 9 7. 3 2. 7	971, 619 260, 153 9, 087	250, 711 304, 190 53, 598	18, 585, 083, 957 17, 348, 363, 000 6, 965, 335, 391	
	155	182, 781, 184	100.0	6 7, 570, 087	3, 429, 019	64, 539, 828, 288	

<sup>In addition to the coal and natural gas included for this group, 1 plant reported the use of petroleum coke with coal and natural gas.
Includes 107,653 short tons of anthracite and 7,462,434 short tons of bituminous coal.</sup> 

Electric power.—Ten percent more electric power was consumed by portland cement mills in 1942 than in 1941. However, the average quantity used per barrel of finished cement produced decreased slightly from 22.2 kilowatt-hours in 1941 to 21.9 kilowatt-hours in 1942.

Electric energy used at portland-cement-producing plants in the United States, 1941-42, by processes, in kilowatt-hours

			- 12 M	A verage electric				
Process		ated at port- ment plants	P	urchased	, Total		Finished cement produced  Barrels	energy used per barrel of cement produced  Kilo- watt- hours
	Active plants	Kilowatt- hours	Active plants	Kilowatt- hours	Kilowatt- hours	Per- cent		
1941 Wet Dry	32 36	<b>643</b> , 610, 788 1, 076, 033, 868		1, 224, 801, 790 700, 009, 725	1, 868, 412, 578 1, 776, 043, 593	51.3 48.7	85, 153, 919 78, 876, 640	
Percent of total elec- tric energy used	68	1, 719, 644, 656 47. 2		1, 924, 811, 515 52. 8	3, 644, 456, 171 100. 0	100.0	164, 030, 559	22. 2
1942 Wet Dry	31 35	656, 101, 658 1, 229, 365, 051	52	752, 007, 188	2, 026, 972, 668 1, 981, 372, 239	49.4	87, 610, 162	22.6
Percent of total elec- tric energy used	66	1, 885, 466, 709 47. 0		2, 122, 878, 198 5 <b>3</b> . 0	4, 008, 344, 907 100. 0	100.0	182, 781, 184	21.9

## SPECIAL CEMENTS

In addition to the standard or general-purpose portland cement that constitutes most of the total production, several special varieties are made. Of these, the low- and moderate-heat and high-early-strength types are the most important, and demand for them has increased sharply in recent years. Demand for the other special cements was considerably below that in 1941.

Prepared masonry mortans.—Production of these mixed materials from 48 plants totaled 2,067,370 barrels and shipments 2,079,015 barrels, valued at \$3,115,799, an average of \$1.50 per barrel. These data are not included in the statistics of this chapter, but the portland cement used in their manufacture is included.

Special portland cements produced and shipped in the United States, 1938-42, by kinds

				Shipments	
Kind and year	Active	Production (barrels)		Val	ue
	plunos	(barrens)	Barrels		
				Total	Average
High-early-strength:					
1938	72	3, 340, 582	3, 385, 523	\$6, 247, 699	\$1.8
1939	79	3, 780, 716	3, 693, 460	6, 964, 608	1.8
1940	88	4, 478, 797	4, 401, 449	8, 243, 315	1.8
1941	90	6, 063, 638	6, 123, 224	11, 443, 792	1.8
1942 Masonry or mortar:	87	7, 523, 647	7, 065, 700	13, 683, 665	1.9
1938	5	04.055	00 00*		
1939	5	84,875	88, 905	124, 239	1.4
1940		173, 737 219, 480	155, 781	211, 711	1.3
1941	,	219, 400	214, 303	308, 333	1.4
1942	1	(1)	(1)	(1)	
Low- and moderate-heat:		(-)	(-)	(+)	(1)
1938	38	4, 181, 568	3, 808, 927	5, 710, 698	1.5
1939	43	5, 564, 921	5, 761, 840	8, 237, 440	1.4
1940	55	8, 559, 487	7, 709, 503	10, 307, 976	1.3
1941	58	11, 290, 232	11, 177, 651	14, 963, 940	1.3
1942	60	13, 020, 467	13, 404, 761	19, 136, 773	1.4
Portland-puzzolan:				,,	
1938	9	198, 268	185, 664	285, 088	1.5
1939	9	337, 187	321, 217	434, 281	1.3
1940	10	413, 870	412, 143	552, 830	1.3
1941	8	441, 500	439, 354	632, 713	1.4
1942	7	324, 002	329, 637	465, 627	1.4
1938	4	900 900	000 04		
1939	3	369, 390	369, 847	1, 351, 875	3.6
1940	3	(1)	(1)	(1)	(1)
1941	4	538, 752	549, 293	2, 191, 289	(1)
1942	5	345, 613	306, 120	1, 214, 422	3.99
	v	010, 010	300, 120	1, 214, 422	3. 9
1938	8	238, 966	232, 319	481, 401	2.0
1939	12	375, 866	375, 027	710, 032	1.8
1940	22	711. 348	719, 022	1, 365, 840	1.9
1941	19	786, 167	806, 364	1, 550, 301	1. 9
1942	17	537, 541	552, 157	1, 100, 296	1. 9
ulfate-resisting:	-			_,,	
1938	- 3	(1)	(1)	(1)	(1)
1939	4	38, 279	27, 362	57, 867	2.1
1940	11	193, 348	200, 090	316, 280	1.58
1941 1942	9	342, 400	353, 885	544, 767	1.5
Aiscellaneous:	8	79, 835	77, 015	136, 939	1.78
1938	15	642, 854	607 000	1 004 000	
1939	15		625, 860	1,004,393	1.60
1940	13	755, 833	775, 179	1,067,699	1.38
1941	13	580, 502 668, 655	577, 579 667, 206	755, 764	1.3
1942	12	242, 170	269, 705	1,058,108	1. 59
	14.	272, 170	208, 100	468, 083	1.7

<sup>&</sup>lt;sup>1</sup> Bureau of Mines not at liberty to publish figures separately.

#### NEW DEVELOPMENTS

To conserve power and grinding equipment and to increase production, emergency alternate specifications <sup>2</sup> approved early in June, reduced the types of portland cement from 5 to 3—general-purpose, moderate-heat, and high-early-strength. These specifications differed from those in effect before the emergency by limiting the maximum specific surface area to not more than 2,000 square centimeters per gram and lowering the minimum requirement to 1,500 square centimeters per gram; by raising the permitted expansion in the autoclave to 1 percent; by eliminating the 28-day test and requiring tests only

<sup>&</sup>lt;sup>2</sup> Federal Specifications Board, Emergency Alternate Federal Specification for Cement, Portland-E-SS-C-191b; Portland-E-SS-C-201a; and Portland-E-SS-C-206a; June 5, 1942. Am. Soc. for Testing Materials, Emergency Alternate Specifications for Portland Cement, A. S. T. M.: Designation EA-C-150-Type I; EA-C-150-Type II; and EA-C-150-Type III; June 6, 1942.

大方式 · 下本 · 東京

at 3 and 7 days; and by permitting the use of TDA in all three types and of vinol resin in the general-purpose and moderate-heat types.

Results of a study <sup>3</sup> on hydrated calcium aluminates yielded fundamental information on phase solubilities and equilibria of the CaO–Al<sub>2</sub>O<sub>3</sub>–H<sub>2</sub>O system.

# NATURAL, MASONRY (NATURAL), AND PUZZOLAN CEMENTS

Production of the natural, masonry (natural), and puzzolan cements declined slightly from 1941. Output of these cements had advanced from 1938 to 1941, in which year annual output was higher than at any time since 1907. In 1942 producers reported consumption of 36,808 short tons of coal and of gas equivalent to 70 tons of coal.

Shipments also declined in 1942 from 1941, and, as production exceeded shipments, stocks on December 31, 1942, were 26 percent

greater than at the end of 1941.

Natural, masonry (natural), and puzzolan (slag-lime) cements produced, shipped, and in stock at mills in the United States, 1938-42

	Prod	uction	Shipn	nents	Stock (Dec. 31)
Year	Active plants	Barrels (376 pounds)	Barrels (376 pounds)	Value	Barrels (376 pounds)
1938	12 12 12 12 12 11	1, 820, 795 2, 439, 110 2, 534, 566 2, 875, 962 2, 560, 425	1, 867, 949 2, 405, 135 2, 514, 597 2, 926, 203 2, 508, 324	\$2, 725, 776 3, 361, 724 3, 386, 801 3, 967, 567 3, 668, 169	373, 816 239, 938 259, 868 1 199, 355 251, 466

<sup>1</sup> Revised figure.

#### FOREIGN TRADE

Because of wartime restrictions, no figures on imports and exports can be published. However, foreign trade of the United States in cement has little effect on the domestic industry; consequently, it is believed that lack of these data will not detract appreciably from the value of this chapter. Foreign-trade figures will be released at the termination of the war so as to preserve the continuity of the statistical record.

Imports.—During the 1935-39 period, imports of hydraulic cement ranged from 619,404 barrels valued at \$615,866 (c. i. f. port of shipment) in 1935 to 1,913,853 barrels at \$1,860,543 in 1939 and had an annual average of 1,544,700 barrels at \$1,345,478. This average represents only 1.4 percent of the average annual consumption of 108,934,353 barrels in the United States during the 1935-39 period. In 1939, the last year with an undisturbed flow of imports, about 97 per cent of total imports of cement originated in Europe, more than half coming from Belgium and about a fourth from Denmark. Following the outbreak of war in Europe in 1939, the conquering of Denmark, Norway, Belgium, and France by Germany in the first half of 1940, and the blockade of Europe by the British Navy, cement imports during 1940 slumped to 538,060 barrels valued at \$506,191.

<sup>\*</sup> Wells, Lansing S., Clarke, W. F., and McMurdie, H. F., Study of the System CaO-Al<sub>2</sub>O<sub>3</sub>-H<sub>2</sub>O at Temperatures of 21° and 90°C: National Bureau of Standards Jour. of Research, vol. 30, May 1943, pp. 367-409.

This quantity represents only 0.4 percent of the apparent consumption (131,734,848 barrels) in the United States in 1940. Importation virtually ceased in 1941, during the first 9 months of which 43,110 barrels valued at \$57,914 were brought into the country. The monthly rate of import in 1941 was 4,790 barrels, compared with 44,838 barrels per month during 1940, a decline of 89 percent. It seems evident that imports in 1942 undoubtedly were insignificant.

Exports.—Exports in the 1935-39 period ranged from 334,673 barrels valued at \$886,560 in 1936 to 1,146,339 barrels at \$2,352,693 in 1939 and had an annual average of 566,778 barrels at \$1,318,248. This average is only 0.5 percent of average annual domestic shipments of cement (107,956,430 barrels) in the United States during 1935-39. In 1940, the last year for which complete data are available, exports increased 45 percent over 1939 to 1,667,595 barrels valued at \$3,294,-118, a quantity representing only 1.3 percent of domestic shipments (132,864,383 barrels) from mills in the United States during the same year. Exports in 1940 were distributed as follows: 73 percent (1,212,909 barrels) to North American countries (including the West Indies), of which more than half went to Panama (Republic and Canal Zone); 26 percent (431,904 barrels) to South American countries, of which three-fourths went to Venezuela; and the remaining 1 percent was distributed to countries in Europe (452 barrels), Asia (7,810 barrels), Africa (14,108 barrels), and Oceania (412 barrels). Exports during the first 9 months of 1941 totaled 1,757,172 barrels valued at \$3,793,511, a monthly rate of 195,241 barrels or 40 percent higher than the 138,966 barrels per month exported in 1940.

Shipments of domestic hydraulic cements to noncontiguous territories of the United States in 1940, the last year for which data were published, were nearly double those in 1939 and totaled 1,461,940 barrels valued at \$2,628,402, of which 47 percent was sent to Hawaii and 46 percent to Puerto Rico. These 1940 shipments represent 1.1 percent of total domestic shipments from mills in the same year.

In 1942, both exports and shipments to noncontiguous countries undoubtedly were greater than in 1941, owing to such factors as increased construction of military and naval facilities by the United States in offshore locations and foreign countries, the accelerated construction of the Pan American Highway, and the continued blockade of European producers from world markets for cement. Partly offsetting these factors, the Army, Navy, and other governmental agencies performing construction work outside the United States have tended to use local or the nearest source of supply of cement to conserve shipping space.

#### WORLD PRODUCTION

World production of hydraulic cements in 1942, based upon the meager data available, is estimated at approximately 72 million metric tons.

Output in most of the countries of the Western Hemisphere doubtless was higher in 1942 than 1941, owing principally to the increased construction of war plants, military facilities, and the Pan American highway. However, in some countries production was below the 1941 level, as in Brazil, where a fuel shortage reportedly curtailed production.

In all European countries, except Spain, production probably was curtailed markedly because of labor and fuel shortages. Military uses undoubtedly consumed most of the product in these countries, and civilian and industrial consumption was kept at a bare minimum as was indicated by the regulation in Germany requiring approval of all purchases exceeding 10 sacks.

In most of the Mediterranean and Near-Eastern countries and in India and Australia production probably gained markedly over 1941, whereas output in the Far Eastern countries declined somewhat. Production in countries in southern and eastern Africa no doubt

increased over 1941.

World production of hydraulic cements, 1937-42, by countries, in metric tons 1 [Compiled by B. B. Waldbauer]

		- 1				
Country	1937	1938	1939	1940	1941	1942
North America:					V	
Canada	975, 231	876, 193	909, 875	1, 200, 143	1, 328, 587	1, 456, 850
Cuba	. (2)	(2)	(3)	(3)	(3)	(3)
Guatemala	(2)	(2)		(3)	(3)	(3)
Mexico	344,693	373, 712	409, 784	484,992	537, 464	(8)
United States	20, 137, 732	18, 279, 156	21, 267, 269	22, 640, 675	28, 465, 880	<b>31,</b> 609, 981
South America:				1 000 501	(m)	(0)
Argentina	1,035,495	1, 245, 458	1, 141, 865	1,088,591		(8)
Bolivia	11,100	18,600	(3)	24, 285		(%)
Brazil	571,462	617,896	697, 793	743,634	767, 506	4 308, 700
Chile	313, 110	363, 987	447, 992	385,091	359, 720	(3)
Colombia	123, 175	141,809	167,000	188,000 16,490	210, 912 18, 631	8
Ecuador	(2)	(2)	15, 445	124, 480	167, 872	8 140, 418
Peru	83,048	101, 380	119, 986			
Uruguay	147,773	158, 359	173, 500	167,880	179,066	(3) (3)
Venezuela	44,626	39,863	39, 130	87,068	(3)	(9)
Europe:	14.000	<b>(0)</b>	/n	(3)	(3)	(3)
Albania	14,000	3, 054, 144	2, 551, 756	3	3	(3)
Belgium	3,008,016		2, 331, 730	\ \int_a\		
Bulgaria	135,000	180,000	%	(3)	1 2	(3)
Czechoslovakia		639, 957	696,000	441,000		/₃<
Denmark		79,740	77,000	(3)	1 3	735
Estonia	65, 931 410, 371	475, 152	563,000	(3) (3)	🖟	· 35
Finland	4, 254, 800	(2)		(3)	000000000000000000000000000000000000000	9999999999
France		15,600,000	(3)	(3)	3	(3)
GermanyAustria	430,000	650,000	(3)	(3)	(3)	(3)
		308,000	3	3	(3)	(3)
Greece		395,000	(3)	3	(3)	(35)
HungaryIreland	. 392,000	110,000	261,000	272,000	(3)	(3)
Italy	4, 359, 112	4,607,454	4,800,000	(3)	(3)	(3)
Latvia		154, 621	164,601	(3)	(3)	(3)
Netherlands		456,000	541,000	(3)	(3)	(3)
Norway		331,600	390,000	(3)	(3)	(3)
Poland	1, 289, 108	1,719,452	(3)	(3)	(3)	(3)
Portugal	254,000	268,000	297,000	271, 173	(3)	186,96
Rumania	456, 311	448, 402	531,000	400,000	(3)	(3).
Spain	379, 751	592, 427	1, 194, 481	1,557,878	(3)	(3)
Sweden		992, 932	1, 184, 991	700,749	(3)	(3)
Switzerland	(2)	6 650, 000	(3)	650,000	7 700,000	7 500,00
U. S. S. R	5, 459, 000	5,696,000	5, 700, 000	5, 800, 000	(3)	(3)
United Kingdom		7,900,000	(8)	(3)	(3)	(3)
Yugoslavia	618, 635	712, 302	663,000	(3)	(3)	(3)
Asia:	1					
China	250,000	24,000	6 540, 000	652, 500	(3)	0000000
Manchuria	7 800, 000	(2)	(3)	(3)	(3)	(3)
Chosen	665,000	(2)	(3)	(3)	(3)	(3)
Hong Kong	.  (2)	110,036	(8)	(3)	(3)	(2)
India, British		(2)	(8)	(3)	(3)	(3)
Indochina		266, 366	305, 800	278, 500	[· (8)	(3)
Tran	(2)	(2)	(3)	(8)	0000000	<u>  (3)</u>
Japan and colonies	6,034,000	5,519,000	5.074.000	7 4, 250, 000	l (2)	

Data cover all hydraulic cements.

Data not available; estimate included in total.

Data not available.
I January to November, inclusive.
January to September, inclusive.
Shipments.

Approximate production.

# World production of hydraulic cements, 1937–42, by countries, in metric tons—Continued

Country	1937	1938	1939	1940	1941	1942
Asia—Continued.						
Netherlands Indies	(2)	(2)	7 170,000	(3)	(8)	(3)
Palestine	161,000	98, 445	112, 350	148, 487	(3)	8
Philippine Islands	150, 374	167, 448	(3)	(3)	\ \alpha\	(3)
Syria and Lebanon	250,000	251,000	227, 285	91, 653	\	250, 000
Thailand (Siam)	77,000	82,000	8 92,000	8 116, 864	(3)	(3)
Turkey	214, 794	267, 568	283, 624	266, 637	(3)	(3)
Africa:			200,021	200, 001	. ()	(7)
Algeria	65,000	(2)	(3)	(3)	(3)	(3)
Belgian Congo	10, 723	16,500	35,000	(3)	3	(3)
Egypt	330,000	375, 763	371, 941	360, 832	420, 107	785
Morocco, French	156,000	165,000	(3)	(3)	(3)	3
Mozambique	14, 957	24, 297	27,618	27, 893	(3)	-(3)
Tunisia	56, 400	68, 700	(3)	(3)	(3)	73
Union of South Africa	839, 526	878, 206	948, 664	831, 018	(3)	(3)
Oceania:			177777	,		
Australia 9	731, 650	862, 539	881,778	879,000	(3)	(3)
New Zealand 8	176, 000	220,000	235,000	(3)	(3) (3)	(3) (3)
	82, 714, 000	85, 859, 000	(10)	(10)	(10)	72, 000, 000

<sup>Data not available; estimate included in total.
Data not available.
Approximate production.
Year ended March 31 of year stated.
Year ended June 30 of year stated.
Estimate not prepared.</sup> 

### STONE

### By OLIVER BOWLES AND M. S. JENSEN

#### SUMMARY OUTLINE

	_		Page
	Page		Lage
General conditions	1221	Crushed and broken stone	1237
Dimension stone	1224	Salient statistics	1237
Salient statistics	1224	Commercial and noncommercial operations.	1240
Building stone		Size of plants	1240
Granite		Methods of transportation	1241
Basalt		Granite	1242
Marble		Basalt	1243
Limestone	1230	Marble	1245
Sandstone	1233	Limestone	1245
Miscellaneous stone	1235	Sandstone	1249
Trends in use of dimension stone	1235	Miscellaneous stone	1250
New developments	1237	Markets	1252
110M (101010httmm)		Markets New developments	1253
	- 17	Foreign trade	1253

#### GENERAL CONDITIONS

Sales of crushed and dimension stone combined were 7 percent greater in 1942 than in 1941 and attained an all-time high record of 195,884,490 short tons. The total value of sales (which, for the first time in history, exceeded \$200,000,000) was 5 percent greater than in 1941. The gains, however, were confined almost exclusively to crushed and broken stone because wartime construction requires very small quantities of building stone. Sales of dimension stone (exclusive of slate) were 31 percent lower in quantity and 22 percent in value. The crushed-stone industry, on the other hand, gained 7 percent in quantity and 8 percent in value. The trends in these two great branches of the stone industries were the same as in 1941, but the downward trend of dimension-stone sales was accelerated, whereas the upward movement of crushed stone was retarded.

The present chapter follows the general plan inaugurated in 1938, whereby the data on dimension stone are separated from those on

crushed stone, except in the introductory general tables.

The tables of this report give the quantities sold or used by producers and the values f. o. b. quarries and mills insofar as these figures are obtainable. Stone quarried and used by producers is considered as sold and is included in the statistics of sales. The data, however, do not include stone made into abrasives (such as grindstones) or that used in making lime and cement. These materials are reported in terms of finished products in the Abrasive Materials, Lime, and Cement chapters of this volume. The following tables show the total sales of stone by kinds, uses, and States:

1221

# Stone sold or used by producers in the United States, 1938-42, by kinds [Quantities approximate]

Year	Gra	nite	Basalt and related rocks (trap rock)		Marble		Limestone	
rear	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
1938 1939 1940 1941 1942	10, 432, 980 12, 041, 360 10, 880, 580 14, 298, 750 14, 064, 780	21, 621, 943 24, 968, 489	16, 091, 250 15, 715, 890 17, 936, 950	15, 185, 652 18, 641, 852	219, 390 228, 080 239, 730 176, 460 169, 500	6, 688, 662 5, 196, 124 4, 785, 710	81, 679, 690 100, 846, 090 112, 658, 060 133, 163, 600 142, 487, 600	94, 817, 48 103, 007, 30 127, 585, 11

Year	Sandstone		Other stone 1		Total	
	Short tons	Value	Short tons	Value	Short tons	Value
1938	6, 314, 430 8, 853, 680 6, 498, 960 7, 592, 820 6, 700, 920	11, 745, 631 8, 513, 654	9, 386, 670 7, 739, 820 9, 939, 380	8, 549, 742 6, 519, 437 8, 587, 509	147, 447, 130 153, 733, 040 183, 107, 960	160, 044, 115 195, 337, 426

i Includes mica schist, conglomerate, argillite, various light-color volcanic rocks, serpentine not used as marble, soapstone sold as dimension stone, and such other stone as cannot properly be classed in any main group.

# Stone sold or used by producers in the United States, 1941-42, by uses

Use	19	941	1942		
	Quantity	Value	Quantity	Value	
Dimension stone: Building stone:					
Rough constructionshort tons_ Cut stone, slabs, and mill blocks	389, 160	\$1,706,591	267, 100	\$1, 354, 087	
Approximate equivalent in short tons Rubbleshort tons	5, 596, 240 426, 850	8, 111, 376	2,848,180 214,100	4, 572, 074	
Monumental stoneshort tons Approximate equivalent in short tons	729, 490 2, 882, 310 237, 440	870, 043 9, 110, 846	544, 450 2, 737, 240	957, 790 8, 976, 566	
Paving blocksnumber_ Approximate equivalent in short tons	1 2, 384, 110 1 20, 850	1 255, 276	225, 910 1, 986, 910 18, 540	188, 830	
Curbing cubic feet Approximate equivalent in short tons	1 820, 470 1 66, 240	1 896, 209	314, 830 25, 380	361, 590	
Flaggingcubic feet_ Approximate equivalent in short tons	990, 900 76, 950	445, 493	679, 990 51, 980	290, 646	
Total dimension stone (quantities approximate, in short tons)	1, 946, 980	21, 395, 834	1, 347, 460	16, 701, 583	
Crushed and broken stone:					
Riprapshort tons_ Crushed stonedo Furnace flux (limestone and marble)do	5, 152, 640 120, 963, 910 27, 436, 440	5, 226, 623 114, 522, 259 20, 069, 296	8, 763, 980 125, 267, 650 30, 262, 910	9, 779, 249 116, 394, 778 24, 152, 113	
Refractory stone 3 do Agricultural (limestone) do Other uses 3 do	2, 254, 120 11, 909, 640 13, 444, 230	3, 279, 104 14, 395, 831 16, 448, 479	2, 718, 090 13, 745, 400 13, 779, 000	3, 999, 929 16, 993, 254	
Total crushed and broken stonedo	181, 160, 980	173, 941, 592	194, 537, 030	16, 981, 113 188, 300, 436	
Grand total (quantities approximate, in short tons)	183, 107, 960	195, 337, 426	195, 884, 490	205, 002, 019	

<sup>&</sup>lt;sup>1</sup> To avoid disclosing confidential information, sandstone paving blocks in 1941 are included under "Curbing."
<sup>2</sup> Ganister (sandstone), mica schist, soapstone, and dolomite.
<sup>3</sup> Includes roofing granules as follows—1941: 177,439 tons, \$715,068; 1942: 212,008 tons, \$832,857. Slate granules used for roofing were produced, as follows—1941: 323,740 tons, \$2,708,246; 1942: 356,510 tons, \$2,955,562.

Stone sold or used by noncommercial producers in the United States in 1942, by uses
[Included in total production]

Use	Short tons	Value	Use	Short tons	Value
Dimension stone: Building stone Rubble Curbing	148, 650 95, 940 1, 470	\$309, 562 241, 359 9, 157	Crushed and broken stone: Riprap	2, 787, 210 15, 449, 080 428, 180 491, 700	\$2, 667, 495 16, 262, 654 375, 259 400, 846
Total dimension stone	246, 060	560, 078	Total crushed and broken	19, 156, 170	19, 706, 254
	r ; '		Grand total	19, 402, 230	20, 266, 332

Stone sold or used by producers in the United States, 1941-42, by States

	194	1	1942		
State					
	Short tons (approximate)	Value	Short tons (approximate)	Value	
	(APP-1)				
Alabama	2, 804, 740	\$3, 745, 651	3, 141, 300	\$3, 738, 90	
Arizona	455, 900	340, 872	227, 220	219, 23	
Arkansas	1 1, 788, 470	1 1, 763, 196	2, 033, 410	2, 152, 95	
California	1 9, 139, 390	17, 535, 017	1 12, 288, 700	1 11, 031, 32	
Colorado	1, 104, 820	1, 073, 400	1 951, 510	1 735, 99	
Connecticut	1 2, 244, 900	1 2, 435, 841	1, 556, 350	1, 692, 39	
Delaware	109, 850	147, 212	(2)	(2)	
lorida	1 4, 065, 450	1 3, 852, 539	1 6, 632, 680	1 5, 733, 69	
leorgia	2, 808, 790	5, 809, 755	1 3, 623, 160	1 6, 620, 63	
Iawaii	1 1, 330, 170	1 2, 149, 535	(2)	(3)	
daho	767, 750	644,006	470, 590	588, 98	
llinois	1 11, 856, 340	1 10, 706, 996	14, 056, 050	12, 686, 7	
ndiana	5, 257, 530	6, 742, 744	1 6, 460, 540	1 7, 007, 24	
owa	5, 790, 920	5, 657, 585	4, 474, 480	4, 849, 80 3, 031, 04	
Kansas	2, 727, 290	3, 171, 598	2, 588, 200	1 5, 454, 9	
Kentucky	1 5, 779, 800	<sup>1</sup> 5, 177, 170	<sup>1</sup> 5, 641, 280	(2)	
Louisiana	(2)			1 556, 6	
Maine	324,060	1, 295, 180	1 196, 010	1, 807, 2	
Maryland	1, 604, 430	2, 218, 478	1, 220, 190 1 1, 800, 600	1 3, 468, 7	
Massachusetts	2, 602, 120	4, 547, 808	16, 093, 050	9, 433, 0	
Michigan	15, 161, 820	8, 349, 607		1 1, 858, 6	
Minnesota		1, 811, 805 1 750	1 1, 451, 210	- 1, 000, 0	
Mississippi			1 9, 235, 540	1 8, 347, 1	
Missouri	6, 501, 460	7, 048, 207 336, 632	393, 200	303, 2	
Montana	455, 680 1 328, 690	1 660, 573	267, 020	630, 4	
Nebraska	183, 170	226, 827	137, 920	196.7	
Nevada	1 167, 270	1 373, 157	237, 090	440, 7	
New Hampshire	3, 206, 050	3, 782, 036	3, 393, 510	3, 776, 7	
New Jersey New Mexico	118, 180	111, 709	515, 240	248, 8	
New York	10, 406, 740	10, 806, 450	11, 244, 670	11, 513, 0	
North Carolina.	3, 820, 200	4, 806, 623	3, 039, 580	3, 774, 4	
North Dakota		19, 713	(2)	(2)	
Ohio	1 13, 842, 870	1 12, 469, 498	14, 831, 660	13, 546, 4	
Oklahoma	1, 876, 570	1, 945, 753	5, 946, 520	3, 172, 5	
Oregon	2, 836, 390	2, 436, 783	2, 596, 030	2, 635, 0	
Pennsylvania.	1 23, 506, 540	1 25, 013, 400	1 23, 131, 670	1 26, 892, 9	
Puerto Rico	675, 970	968, 448	(2)	(2)	
Rhode Island	212, 580	493, 715	191, 420	` 351, 6	
South Carolina	2, 055, 090	2, 574, 797	2, 040, 610	2, 624, 2	
South Dakota	1 401, 550	1 1, 189, 564	714, 750	1, 763, 7	
Tennessee	7, 896, 970	9, 157, 673	7, 716, 540	9, 018, 2	
rexas.	3, 497, 720	2, 908, 364	3, 772, 040	3, 658, 8	
Utah	408, 140	340, 551	285, 170	318, 2	
Vermont.		4, 190, 112	244, 110	3, 831, 3	
Vermont Virginia	9, 195, 450	9, 586, 541	7, 052, 930	7, 938, 3	
Washington	2, 148, 970	1, 757, 873	1, 965, 820	1, 809, 7	
West Virginia	1 4, 547, 200	1 5, 988, 840	3, 223, 330	3, 238, 0	
Wisconsin	4, 376, 720	5, 666, 120	4, 492, 740	6, 309, 3	
Wyoming		737, 455	179, 290	207, 1	
Undistributed	672, 080	563, 267	4, 129, 560	5, 786, 1	
	183, 107, 960	195, 337, 426	195, 884, 490	205, 002, 0	

<sup>&</sup>lt;sup>1</sup> To avoid disclosing confidential information, certain State totals are incomplete, the figures not included being combined under "Undistributed."

<sup>3</sup> Included under "Undistributed."

### **DIMENSION STONE**

Dimension stone and crushed stone are so diverse in character and use that they are considered in separate sections of this chapter. The term "dimension stone" is applied to blocks or slabs of natural stone, most of which are cut to definite shapes and sizes. The principal uses of dimension stone are for construction of masonry walls and for memorials. Crushed and broken stone, on the other hand, consists of irregular fragments or grains, sized chiefly by mechanical screening or air separation. The principal uses are as roadstone, concrete aggregate, railroad ballast, furnace flux, and a great variety of industrial applications that have little or no relation to masonry construction.

Dimension-stone producers may be divided into three main groups upon the basis of plant operation. The first group quarries stone and sells it as rough blocks or slabs; the second quarries stone and also manufactures it into finished products; and the third buys sawed slabs or rough blocks of stone and manufactures them into finished products but does not operate quarries. The Bureau of Mines statistical canvass covers the first and second groups, but as the third group comprises manufacturers rather than quarrymen it is canvassed by the Bureau of the Census. Bureau of Mines statistics are compiled from reports of quantities and values of original sales; hence they include some material sold as rough blocks and some sold as finished products.

Total sales of dimension stone in 1942 declined 32 percent in quantity and 24 percent in value compared with 1941. These figures include slate, but details of the slate industry are given in the separate chapter on Slate. Basalt in the form of rubble and sandstone used for rough construction and rubble made gains in quantity, but all varieties of stone suffered declines in value of sales that ranged from 7 percent for basalt to 43 percent for limestone.

The following table presents salient statistics for 1941 and 1942.

Dimension stone sold or used by producers in the United States, 1941-42, by kinds and uses

Kind and use		194	1942		
And and use	1941	Total	Percent of change		
Granite: Building stone:					
Rough constructionshort tons_					
Valuesnort tons_		36, 380	-78.3		
Average per ton	\$298, 253	\$132, 276	-55.6		
Cut stone, slabs, and mill blockscubic feet_	\$1.78 736,730	\$3.64	+104.5		
	\$1,853,203	413, 180 \$1, 030, 223	-43.9 -44.4		
Average per cubic foot	\$2, 52	\$2, 49	-1.2		
Rubbleshort tone	277, 950	215, 730	-22.4		
Value	\$349, 739	\$404, 460	+15.6		
Monumental stone	2, 576, 550	2,442,630	-5.2		
Value	\$7, 489, 197	\$7,092,572	-5.3		
Average per cubic foot	\$2.91	\$2.90	3		
Paving blocksnumber_		1, 986, 910	-16.7		
Value	\$255, 276	\$188, 830	-26.0		
Curbingcubic feet	528, 420	200, 540	-62.0		
Value	<b>\$</b> 585, 808	\$232, 392	-60.3		
Total:					
Quantityapproximate short tons	700 100	F00 150			
Value	782, 120 \$10, 831, 476	522, 170	-33. 2		
	φ10, 031, 470	\$9,080,753	-16.2		

Dimension stone sold or used by producers in the United States, 1941-42, by kinds and uses—Continued

		1942-		
Kind and use	1941	Total	Percent of change	
Basalt and related rocks (trap rock):				
Building stone: Rough constructionshort tons	10 170	4, 880	-52.0	
Value	10, 170 \$17, 182	\$12,652	-26.4	
Value	\$1.69	\$2.59	+53.3	
Rubbleshort tons	130	7,870	+5, 953.8	
Value	\$550	\$3,869	+603.	
Total:				
Quantityshort tons_	10, 300	12, 750	+23.8	
Quantity short tons Value	10, 300 \$17, 732	12, 750 \$16, 521	6.8	
Marble:				
Building stone (cut stone, slabs, and mill blocks)cubic feet	511, 810	278, 460 \$1, 567, 736	-45.0	
Value Average per cubic foot cubic feet cubic feet cubic feet.	\$2,748,572	\$1, 567, 736	-43.	
Average per cubic foot	\$5. 37	\$5. 63	+4.	
Monumental stone cubic feet	305, 760	294, 610	-3.	
Value	\$1,621,649	\$1,883,994	+16.	
Average per cubic foot	\$5. 30	\$6. 39	+20.	
Total:				
Quantityapproximate short tons	69, 300	48, 590	-29.	
Quantityapproximate short tons	\$4, 370, 221	\$3, 451, 730	-21.0	
imestone:				
Duilding stone	100			
Rough constructionshort tons_	106, 290 \$367, 995	96, 610	-9.	
Value	\$367, 995	\$209, 313	-43.	
Average per ton	\$3.46	\$2.17	-37.	
A verage per ton Cut stone, slabs, and mill blocks	3, 834, 860 \$2, 909, 728 \$0. 76	1, 891, 930 \$1, 582, 254	-50.	
Value	\$2,909,728	\$1, 582, 254	-45.	
Average per cubic foot	\$0.76	\$0.84	+10.	
Rubblesnort tons	405, 220	221, 180	-45. -26.	
Value	\$439, 479	100 700	-20. -52.	
Value	210, 290 \$62, 794	\$324, 097 100, 790 \$28, 823	-54.	
	Ψ02,101	Ψ20, 020		
Total:	010.000	400.070	40	
Quantity approximate short tons Value	813, 620	462, 970 \$2, 144, 487	-43.	
Value	\$3, 779, 996	\$2, 144, 487	-43.	
andstone:			100	
Building stone:				
Building stone:  Rough constructionshort tons	31,850	84, 980 \$174, 730	+166.	
Value	\$106, 426 \$3. 34	\$174,730	+64. -38.	
Average per ton	\$5. 54 *10. 040	\$2.06	-30. -48.	
ValueCubic feet	512, 840 \$599, 873	264, 610 \$391, 861	-34.	
	\$1. 17	\$1.48	+26.	
Average per cubic footshort tons_	33, 990	77, 400	+127.	
Value	\$46, 253	\$166, 369	+259.	
Paying blooks number	(1)	4200,000	-100.	
Value	(1)		100.	
Curbing cubic feet.	· 1 292, 050	114, 290	1 -60.	
Value.  Curbing cubic feet.  Value.	<sup>1</sup> \$310, 401	\$129, 198	1 58.	
Flaggingcubic feet_	743, 680	559,060	-24.	
Value	<b>\$366, 426</b>	\$251, 354	-31.	
Total:				
Quantity approximate short tons.	183, 040	232, 850	+27.	
Quantityapproximate short tons Value	\$1, 429, 379	\$1, 113, 512	-22.	
Iiscellaneous stone: 2				
Building stonecubic feet_	870 800	536 450	-38.	
Valua	870, 800 \$916, 735	536, 450 \$825, 116	-10.	
Value	\$1.05	\$1.54	+46.	
Rithble ghort tong I	12, 200	22, 270	-+82.	
Value	\$34,022	\$58, 995	十73.	
Flaggingcubic feet_	36, 930	20, 140	-45.	
Valuecubic feet_ Value	36, 930 \$16, 273	22, 270 \$58, 995 20, 140 \$10, 469	-35.	
Total.				
Quantity approximate short tons	88, 600	68, 130	-23.	
Quantityapproximate short tons Value	\$967,030	68, 130 \$894, 580	-23. -7.	
atal dimension stone evaluding class.				
otal dimension stone, excluding slate:	1, 946, 980	1 347 460	-30.	
Quantityapproximate short tons	\$21 305 834	\$16, 701 582	-30. -21.	
lete or dimension stone & onnewimete short tone	\$21, 395, 834 180, 990	107, 030	-21.	
Value	\$4, 409, 834	1, 347, 460 \$16, 701, 583 107, 030 \$2, 955, 807	-33.	
	¥-, 100, 001			
Cotal dimension stone, including slate:	0 107 070	1 484 400	91	
Quantity approximate short tons Value	2, 127, 970	1, 454, 490 \$19, 657, 390	-31. -23.	
VAIDE	\$25, 805, 668	φισ, υσ <i>ι</i> , σθΟ	-20.	

<sup>&</sup>lt;sup>1</sup> To avoid disclosing confidential information, paving blocks in 1941 are included under "Curbing."

<sup>2</sup> Includes soapstone, mica schist, volcanic rocks, argillite, and other varieties that cannot be classified in the principal groups.

<sup>3</sup> Details of production, by uses, are given in the chapter on Slate in this volume.

#### BUILDING STONE

The use of stone as a material of construction predates the most ancient historic records, and building stone is still the principal form in which dimension stone is sold. The following table gives the quantity and value of each kind of stone used for construction in 1942.

Building stone sold or used by producers in the United States in 1942, by kinds

				Rot	ıgh		
	Kind		Constr	uction	Architectural		
			Cubic feet	Value	Cubic feet	Value	
GraniteBasalt			580, 610 59, 150	\$132, 276 12, 652	81, 680	\$86, 736	
Marble Limestone Sandstone Miscellaneous			1, 332, 570 1, 087, 290 536, 450	209, 313 174, 730 825, 116	58, 800 866, 540 156, 950	111, 722 257, 212 178, 073	
			3, 596, 070	1, 354, 087	1, 163, 970	633, 743	
		Fini	shed				
Kind	Sawe	d¹	Cu	t 1	Tot	al	
	Cubic feet	Value	Cubic feet	Value	Cubic feet	Value	
GraniteBasalt	237, 320	\$556, 687	94, 180	\$386,800	993, 790 59, 150	\$1, 162, 499 12, 652	
Marble Limestone Sandstone	66, 650 187, 370 78, 940	315, 129 132, 724 108, 739	153, 010 838, 020 28, 720	1, 140, 885 1, 192, 318 105, 049	278, 460 3, 224, 500 1, 351, 900 536, 450	1, 567, 736 1, 791, 567 566, 591 825, 116	
Miscellaneous							

<sup>&</sup>lt;sup>1</sup> For granite, sawed stone corresponds to dressed stone for construction work (walls, foundations, bridges) and cut stone to architectural stone for high-class buildings.

#### GRANITE

Sales of granite in the form of dimension stone declined 33 percent in quantity and 16 percent in value in 1942 compared with 1941. Rough-construction building stone declined greatly, although dressed stone gained moderately. Sales of memorial granite were a little lower than in 1941. The value per cubic foot of dressed building stone declined from \$4.41 in 1941 to \$2.85 in 1942, and the value of dressed monumental stone increased from \$6.35 to \$7.22. Sales of paving stones and curbing declined greatly. Building stone, paving stones, and curbing are all associated closely with types of construction that receive very little encouragement in a time of war. Sales of monumental stone, however, depend principally on buying power, which was high in 1941, and their moderate declines may be attributed to shortage of labor and materials rather than to recession in market demands.

# Granite (dimension stone) sold or used by producers in the United States in 1942, by States and uses

					Buil	ding					Monun	nental							
			Rot	ıgh	,	Dre	hass	Rul	nhle	Rot	ıgh	Dre	hass	Paving blocks		Curbing		Total	
State	Active plants	Constr	uction	Archit	ectural			1041	, DIO	1,00			350 <b>u</b>						
		Short tons	Value	Cubic feet	Value	Cubic feet	Value	Short tons	Value	Cubic feet	Value	Cubic feet	Value	Number	Value	Cubic feet	Value	Short tons (ap- proxi- mate)	Value
California	16 5 5 20 10 4 14 19	(1) 7, 360	7, 569	(1) 2, 250 (1) (1)	(1) \$3, 700	228, 740 (¹)	(1)	5, 940 (1) 5, 220 20, 660 3, 330 39, 950 14, 540	30, 587 2, 042 77, 104	(1) (1) 628, 270 12, 270 20, 090 243, 140 15, 790	\$43, 854 (1) (1) 799, 869 8, 488  55, 454 232, 415 31, 580	(1) (1) 140, 860 7, 720 (1) 29, 760 80	(1) 199, 262 351	(1) 1, 004, 410 376, 950		2,050	1, 855 656	41, 630 49, 790 24, 090 2, 030	\$268, 253 21, 060 63, 914 1, 547, 831 270, 316 85, 329 951, 430 446, 884 34, 411
Montana New Hampshire New Jersey New York North Carolina Oklahoma Pennsylvania Rhode Island South Carolina South Carolina	7 5 1 5 7 10 13 3 4	3, 080 260 (1) 	2, 080 (¹)	200 50 (1) 18, 860 200	205 (1) 13, 477	(1)	812 43, 100  (1) 200	(1) 5, 310	(1) 11, 315 73, 039 99, 786	34, 290	1, 530 8, 160 	(1)	136, 736	(1) 139, 850 (1)	(1) 13, 924 (1)	(1) (1) (1) (1) (1)	(1) (1)	260 3, 370 14, 830	7, 502 109, 790 2, 285 30, 090 221, 011 343, 837 270, 628 168, 804 (1) 792, 419
Texas Vermont Virginia Washington Wisconsin Undistributed	7 8 1 3 14	2, 490		7, 840 (1) 52, 280	5, 840 (1) 62, 800	(1) 66, 540	40, 860 (1) 226, 974		(¹) 10, 986	12, 320 629, 220 (1) (1) 17, 330 212, 330	24, 372 2, 051, 727 (1) (1) 29, 674 421, 264	10, 850 (1) 59, 430 22, 760	(1) 705, 731 193, 353	(¹) (¹) 465, 700	(1) (1) 50, 518		54, 447	33, 640 51, 610 (1) (1) 10, 350 29, 310	792, 419 174, 039 2, 057, 567 (1) (1) 795, 365 417, 988
Average unit value Short tons (approxi- mate)	190	36, 380 (2)	132, 276 \$3. 64		86, 736 \$1.06		943, 487 \$2. 85	215, 730	\$1.87		4, 031, 498 \$2. 00		3, 061, 074 \$7. 22		188, 830 \$0. 10	200, 540  16, 550	232, 392 \$1. 16		9, 080, 753 \$17. 39

<sup>1</sup> Included under "Undistributed."

<sup>2580,610</sup> cubic feet (approximate).

The following tables show sales of monumental granite in the Quincy (Mass.) and Barre (Vt.) centers.

Monumental granite sold by quarrymen at Quincy, Mass., 1938-42 1

Year	Active plants	Cubic feet	Value	Year	Active plants	Cubic feet	Value
1938 1939 1940	3 3 3	33, 300 25, 620 24, 540	\$73, 832 61, 955 60, 139	1941 1942	3 3	26, 670 16, 738	\$65, 062 46, 079

<sup>1</sup> Quincy granite is sold also for construction, curbing, rubble, riprap, and crushed stone.

Monumental granite sold by quarrymen in the Barre district, Vermont, 1938-42 1

Year	Cubic feet	Value	Year	Cubic feet	Value
1938	605, 660 684, 310 601, 190	\$1, 849, 607 2, 029, 801 2, 039, 960	1941 1942	764, 280 612, 220	\$2, 431, 152 2, 035, 327

<sup>1</sup> Barre granite is sold also for construction and crushed stone.

Estimated output of monumental granite in the Barre district, Vermont, 1940-42 1

	1940	1941	1942
Total quarry output, rough stock cubic feet Shipped out of Barre district in rough do Manufactured in Barre district do Light stock consumed in district do Dark stock consumed in district do Number of cutters in district Average daily wage Average number of days worked	548, 412 109, 682 438, 730 274, 206 164, 524 1, 295 \$8. 50 220	668, 544 133, 709 534, 835 334, 272 200, 563 1, 295 \$9.00 230	750, 000 150, 000 600, 000 468, 750 281, 250 1, 295 \$9, 50
Total pay roll for year.  Estimated overhead.  Estimated value of light stock.  Estimated value of dark stock.  Estimated polishing cost.  Output from saws.  Total value of granite.	\$2, 421, 650 1, 210, 825 1, 199, 651 874, 033 346, 980 115, 660 6, 168, 799	\$3, 729, 600 1, 864, 800 1, 398, 605 1, 097, 367 422, 988 140, 996	\$2, 829, 575 1, 414, 787 1, 640, 625 1, 265, 625 474, 525 158, 175 7, 783, 312

<sup>&</sup>lt;sup>1</sup> Through the kindness of the Granite Manufacturers' Association, Barre, figures covering the entire granite industry of the Barre district are given in this table to supplement figures of sales reported by quarrymen.

### BASALT AND RELATED ROCKS (TRAP ROCK)

Because of its dark color, basalt is not used extensively for building. The tonnage sold in 1942 was somewhat higher than in 1941, but the value per ton declined from \$1.72 to \$1.30. Sales for rough construction were less than half as great as in 1941; but rubble sales, which were insignificant in 1941, increased greatly. Basalt is not important as a building stone, and demands for it fluctuate greatly from year to year. Some of these dark rocks are used for memorials, but such stones are classed commercially as black granites and are therefore included with the figures for monumental granite.

Basalt and related rocks (trap rock) (dimension stone) sold or used by producers in the United States in 1942, by States and uses

			Buildin	ng stone		То	tal
State	Active	Rough cor	nstruction	Rub	ble	Short	
		Short tons	Value	Short tons	Value	tons	Value
Colorado	2 1 1 1	(1)	(1) (1)	(1) (2) (3) (3) (4)	(1) (1) (1) (1) (1)	0000000	0000000
New Jersey Oregon Pennsylvania Undistributed	2 3 1	(1) (1) 4,880	(1) (1) \$12,652	(1) (1) 7,870	(1) (1) \$3, 869	2, 100 (1) 10, 650	(1) \$5, 512 (1) 11, 009
Average unit value	13	2 4, 880	12, 652 \$2. 59	7, 870	3, 869 \$0. 49	12, 750	16, 521 \$1. 30

<sup>1</sup> Included under "Undistributed."

#### MARBLE

Sales of marble blocks in 1942 declined 30 percent in quantity and 21 percent in value compared with 1941. Trends in marble sales were similar to those in granite, in that building marble suffered serious declines, but sales of monumental marble were sustained almost at 1941 levels. Munition factories, barracks, and defense housing—the types of buildings that dominated the construction field in 1942—do not have marble halls. The unit value of finished monumental marble made a decisive gain. Georgia sales were maintained at a level comparable with that of 1941, but this condition was exceptional.

Marble (dimension stone) sold by producers in the United States, 1941-42, by uses

	19	41	194	12
Use The Control of th	Cubic feet	Value	Cubic feet	Value
Building stone: Rough: Exterior Interior 2 Finished: Exterior Interior	31, 300 67, 500 153, 360 259, 650	\$63, 647 175, 729 731, 479 1, 777, 717	(1) 1 58, 800 66, 590 153, 070	(1) 1 \$111,722 260,768 1,195,246
Total exterior Total interior	184, 660 327, 150	795, 126 1, 953, 446	1 211, 870	1 1, 306, 968
Total building stone	511, 810	2, 748, 572	278, 460	1, 567, 736
Monumental stone: Rough Finished	61, 790 243, 970	68, 165 1, 553, 484	18, 450 276, 160	23, 489 1, 860, 50
Total monumental stone	305, 760	1, 621, 649	294, 610	1, 883, 99
Total building and monumentalApproximate short tons	817, 570 69, 300	4, 370, 221	573, 070 48, 590	3, 451, 73

<sup>&</sup>lt;sup>1</sup> A small quantity of rough exterior building marble included under rough interior building marble. <sup>2</sup> Includes onyx for the manufacture of mantels, lamp bases, desk sets, clock cases, and novelties.

<sup>&</sup>lt;sup>2</sup> 59,150 cubic feet (approximate).

Marble (dimension stone) sold by producers in the United States in 1942, by States and uses

		Bı	ilding	Mon	umental		Total	le di L
	Active					Qua	ntity	
State	plants	Cubic feet	Value	Cubic feet	Value	Cubic feet	Short tons (ap- proxi- mate)	Value
Alabama Arkansas California Georgia Maryland Massachusetts Minnesota Missouri North Carolina Tennessee Utah Vermont Virginia Undistributed	2 1 1 1 1 1 4 1 7 1 5	(1) 3, 400 (1) 50, 960 140 1, 300 2, 980 32, 400 (1) (1) (1) 76, 850	(1) \$8,000 (1) 236, 492 1, 732 3, 132 11, 750 130, 717 675, 447 3, 970 (1) 496, 496	(1) 300 163, 150 10, 340 9, 600 (1) 9, 960 (1) 101, 260	(1)	(1) 3,700 (1) 214,110 11,640 2,980 42,000 (1) 117,990 2,400 (1) (1) 178,110	(1) 320 (1) 18,200 10 990 210 3,480 (1) 10,030 200 (1) 15,150	(1) \$8, 75( (1) 1, 227, 337 1, 732 71, 107 11, 750 153, 988 (1) 759, 085 3, 970 (1) (1) 1, 214, 013
Average unit value Short tons (approximate)	27	278, 460 23, 550	1, 567, 736 \$5. 63	294, 610 25, 040	1, 883, 994 \$6. 39	573, 070	48, 590	3, 451, 730 3 \$6. 02

1 Included under "Undistributed."

<sup>2</sup> Figures represent onyx rough blocks for the manufacture of mantels, lamp bases, desk sets, clock cases, and novelties.

Average value per cubic foot.

#### LIMESTONE

Limestone in block form is used almost exclusively for building purposes. Small quantities are employed for flagging, but employment for memorials is negligible. Limestone is used more extensively than any other type of building stone, and Indiana producers supplied about 75 percent of the rough architectural and finished (sawed and cut) limestone sold in 1942. Dimension limestone sold in 1942 was 43 percent less both in quantity and value than in 1941. This drastic decline is due to the fact that limestone sales depend almost exclusively on erection volume of the higher types of buildings, such as stores, churches, schools, post offices, courthouses, libraries, office buildings, and other similar edifices, the construction of which was virtually lat a standstill in 1942. Unit prices of the various classes of limestone fluctuated considerably. Rough construction stone declined from \$3.46 to \$2.17 a ton, whereas cut stone, slabs, and mill blocks increased from 76 to 84 cents a cubic foot.

# Limestone (dimension stone) sold or used by producers in the United States in 1942, by States and uses

			, ,	\ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \	Buil	ding					. ,		
			Rot	ugh		Finished	l (cut and	Rubble		Flagging		Total	
State	Active plants	Construction		Architectural		sawed)		rappie					
•		Short tons	Value	Cubic feet	Value	Cubic feet	Value	Short tons	Value *	Cubic feet	Value	Short tons (ap- proxi- mate)	Value
Alabama	_ 2	(¹) 230	(1)	(1)	(1)							(1)	(1) \$952
California	- 5 1	230	`\$650	2, 570	\$4,490			(1)	(1)	(1)	(1)	400 190	\$952 4,490
Georgia.	1 9	(1)	(1)					670 9, 870	\$1,070 15,458			670 10, 680	1,070
Indiana	16			526, 620	160, 117	901, 680	\$1,168,683	12, 140	5, 803	(1)	(1)	115, 640	18, 407 1, 334, 603
Iowa Kansas Kentucky	15 9	3, 700 12, 500 9, 510	3, 265 21, 550 33, 670	108, 150 (¹)	20, 155 (1)	(1)	(1)	1, 420 9, 730 (1)	1, 252 9, 990 (¹)	930 (¹)	\$132 (¹)	5, 160 34, 820 9, 970	4, 649 98, 919 34, 299
Michigan	3 6 11	(1) 550 43, 950	6,600 87,890	(1)	(1)	(1)	(1)	(1) 4, 120 34, 330	(1) 5, 630 57, 117	(¹) 4, 620	(¹) 1, 916	7, 110 78, 660	(1) 38, 05 146, 92
Montana New YorkOhio.	1 4 8	(1) 2, 750	(1) 4, 084	(1)	(1)			(1) 4,400	(1) 4,066	2,430	208	(1) 8,470 7,360	(1) 12, 31 8, 35
OklahomaPennsylvaniaPuerto Rico	18 4	7, 660 (¹)	8, 614 (¹)					(1) 8,510 (1)	(1) 10, 402 (1)	8, 310	1,063	16,770	(1) 20, 07 (1) (1)
South Dakota	4 6	360 (1)	417 (¹)	(1)	(1)	(1)	(1)	5, 860 12, 750	6, 360 28, 687	(1)	(1)	6, 220 16, 950	6, 77'
Virginia West Virginia	1 4 2 16	(1)	(1)	204, 500	55, 606	(1)	(1)	(1) (1) (1) 11, 050	(1) (1)			(1) 4,840 (1)	(1) 7, 05: (1)
Wisconsin Undistributed	- 10	15,400	42, 573	24, 700	16, 844	123, 710	156, 359	106, 330	23, 821 154, 441	50, 540 33, 960	17, 991 7, 513	38, 520 100, 540	141, 15 157, 57
Average unit value	153	96, 610	209, 313 \$2. 17	866, 540	257, 212 \$0. 30	1, 025, 390	1, 325, 042 \$1, 29	221, 180	324, 097 \$1. 47	100, 790	28, 823 \$0, 29	462, 970	2, 144, 487 \$4, 68
Short tons (approximate)		(3)		62, 820		74, 280				8, 080			

<sup>1</sup> Included under "Undistributed."

<sup>1,332,570</sup> cubic feet (approximate).

The following tables show detailed figures, by uses, for limestone produced near Bedford and Bloomington, Ind., and Carthage, Mo., over a 5-year period.

Limestone sold by producers in the Indiana oolitic-limestone district, 1938-42, by classes

•				Const	ruction			
Year		Rough	ı block	Sawed and	semifinished	Cut		
		Cubic feet	Value	Cubic feet	Value	Cubic feet	Value	
1938		2, 090, 110 2, 462, 860 1, 395, 910 1, 047, 000 526, 620	\$619, 602 845, 252 425, 990 309, 444 160, 117	914, 180 1, 277, 730 994, 370 1, 029, 970 135, 360	\$561,767 784,247 573,368 567,706 98,518	1, 147, 620 1, 534, 530 831, 900 826, 510 766, 320	\$2, 044, 216 2, 470, 724 1, 125, 825 1, 177, 651 1, 070, 164	
Year	Consti	ruction—Con Total	tinued	Other	r uses	Total		
	Cubic feet	Short tons (approxi- mate)	Value	Short tons	Value	Short tons (approxi- mate)	Value	
1938	4, 151, 910 5, 275, 120 3, 222, 180 2, 903, 480 1, 428, 300	310, 000 383, 000 233, 600 210, 500 103, 500	\$3, 225, 585 4, 100, 223 2, 125, 183 2, 054, 801 1, 328, 800	41, 610 247, 680 79, 730 135, 610 87, 770	\$26, 595 117, 200 40, 676 98, 547 69, 404	351, 610 630, 680 313, 339 346, 110 191, 270	\$3, 252, 180 4, 217, 423 2, 165, 859 2, 153, 348 1, 398, 204	

Indiana limestone sold by mills in the district not operated by quarry companies and by mills of quarry companies from stock obtained at quarries other than their own, 1938–42, by classes

Year	Sawed a finis		С	ut	Total		
	Cubic feet	Value	Cubic feet	Value	Cubic feet	Value	
1938	110, 670 108, 360 272, 510 86, 690	\$69, 896 50, 338 182, 239 47, 502	1, 136, 410 1, 839, 520 1, 034, 100 690, 250	\$1,703,254 2,966,530 1,629,273 1,043,774	1, 247, 080 1, 947, 880 1, 306, 610 776, 940	\$1,773,150 3,016,868 1,811,512 1,091,276	
1942: Mills not operated by quarry companies Mills of quarry companies from stock obtained at	54, 680	17, 128	287, 130	511,021	341,810	528, 149	
quarries other than their own	(1)	(1)	1 162, 820	1 235, 291	162, 820	235, 291	
	1 54, 680	1 17, 128	. 1 449, 950	1,746,312	504, 630	763, 440	

<sup>&</sup>lt;sup>1</sup> A small amount of sawed and semifinished stone included under cut stone.

Limestone and marble sold by producers in the Carthage district, Jasper County, Mo., 1938-42, by classes

		Dime	nsion sto	ne (rougl	and dr	essed)		Othe	r 11595	Total		
		Building Monu		mental		Total		O ULIC	abob			
Year	Cubic feet	Value	Cubic feet	Value	Cubic feet	Short tons (ap- proxi- mate)	Value	Short tons	Value	Short tons (ap- proxi- mate)	Value	
1938 1939 1940 1941 1942	113, 940 180, 040 124, 180 50, 000 22, 580	248, 498 219, 361	8, 400 8, 430	\$18, 831 18, 603 18, 844 19, 868 23, 271	122, 390 188, 440 132, 610 58, 680 32, 170	15, 730 11, 070 4, 900	\$319, 767 467, 569 267, 342 239, 229 123, 852	60, 580	128, 627 414, 770	76, 310 101, 460 257, 930	395, 96 653, 99	

#### SANDSTONE

Sales of sandstone increased 27 percent in quantity, but their value was 22 percent less than in 1941. The gains in quantity sold were all of relatively low-priced rough construction stone and rubble, hence the low sales value. Sales of cut stone, slabs, and mill blocks declined 48 percent, but the value per cubic foot increased from \$1.17 to \$1.48. Curbing and flagging sales were far below those of 1941. The sandstone paving-block industry has almost disappeared. The number of active sandstone plants declined from 93 to 82.

Ohio is the leading producer, its quarries supplying 44 percent of the total value of output in 1942. The largest quarries are in the Amherst area in the northern part of the State. New York, Pennsylvania, Tennessee, and Massachusetts follow in order of sales value. The thin-bedded ornate sandstones of the Crab Orchard area, Cumberland County, Tenn., have attracted considerable attention during

recent years.

The second table following presents a 20-year history of the bluestone industry. This type of sandstone, which has remarkable splitting properties, is used as a building stone and for curbing and flagging. Sales in 1942 were down 35 percent in quantity and 34 percent in value compared with 1941.

# Sandstone (dimension stone) sold or used by producers in the United States in 1942, by States and uses

					Bui	lding				Ru	bble	Cur	bing	Flag	gging	T	otal
State	Active		h con-		archi-		Dre	essed	. X								
State	plants	stru	ction ————	tect	tural	Sa	wed	C	ut	Short tons	Value	Cubic feet	Value	Cubic	Value	Short tons (approx-	Value
		Short tons	Value	Cubic feet	Value	Cubic feet	Value	Cubic feet	Value						imate)		
Arizona	1		(1) (1)													(1)	(1)
Dalifornia Dolorado Donnecticut	9 3 1	1, 200 11, 420 (1)	\$6, 265 12, 610 (1)							5, 150 20				18, 210 2, 670	\$8, 387 2, 400	(1) (1) 7,770 11,650	15, 03
Kansas Maryland Massachusetts Michigan	1 3 1	(1) 60 350	(¹) 1, 700					9, 420	\$44, 325		(1)			1,800 (¹)	1, 833 (¹)		(1)
Minnesota	1		(1)					950	2, 500	130	750					480 80	2, 450 2, 500
New York 2 Dhio Pennsylvania 3 outh Dakota	18 7 16 1	(1) (1) 540 8, 380 (1)	(1) 1, 381	156, 950	\$178,073	71, 260	(1) \$87, 391	(¹) 15, 420	(1) 40,050	31, 370 310 5, 950	47, 519 1, 400 17, 148	51, 410 62, 030 850	\$56, 898 71, 855 445	58, 740 359, 430 49, 620	49, 103 112, 700 37, 356	49, 070 18, 520	
Cennessee Cexas Vermont Virginia	3 1 1 6	(¹) 200	(1)			 				7, 260 (1) 2, 820	39, 944 (¹) 4, 229			31, 220	27, 489	(i) 9,700 (i) 2,820	(1) 4, 229
Vashington Vest Virginia	1 2	(1)	(1)			(1)	(1)	(1)	(1)	350	400			10, 400 (¹)	4, 296 (¹)	1, 380	5, 021 (1)
Visconsin Indistributed	3	62, 830	135, 302			7, 680	21, 348	(1) 2, 930	(¹) 18, 174	(1) (1) 24, 040	(1) (1) 46, 836			26, 970	7, 790	(i) 88, 230	(1) 191, 871
verage unit valuehort tons (approximate)	82	84, 980 (4)	174, 730 \$2. 06	156, 950 11, 380	178, 073 \$1. 13	78, 940 5, 790	\$1.38	28, 720 2, 180	105, 049 \$3. 66	77, 400	166, 369 \$2, 15	114, 290 8, 830	129, 198 \$1. 13	559, 060 42, 290	251, 354 \$0. 45		1, 113, 512 \$4. 78

<sup>&</sup>lt;sup>1</sup> Included under "Undistributed."

<sup>2</sup> Includes 108,440 cubic feet of bluestone (approximately 12,800 short tons) valued at \$128,169 sold for construction, curbing, and flagging.

<sup>3</sup> Includes 75,030 cubic feet of bluestone (approximately 6,340 short tons) valued at \$38,618 sold for construction, curbing, and flagging.

<sup>4</sup> 1,087,290 cubic feet (approximate).

Bluestone (dimension stone) sold or used in the United States, 1923-42 1

Year	Cubic feet	Value	Year	Cubic feet	Value	
1923 1924 1925 1926 1927 1927 1928 1930 1931	618, 360 769, 240 987, 300 692, 640 815, 730 891, 190 670, 020 611, 240 356, 210 185, 960	\$747, 422 875, 734 910, 585 885, 597 1, 000, 217 1, 014, 843 773, 532 749, 703 427, 801 185, 643	1933 1934 1935 1936 1937 1938 1939 1940 1941	116, 246 181, 968 215, 150 343, 040 308, 740 329, 670 254, 440 256, 900 284, 190 183, 470	\$123, 867 168, 720 203, 537 332, 749 346, 349 369, 857 319, 405 272, 501 252, 313 166, 787	

<sup>1</sup> New York and Pennsylvania are the only States that produce bluestone.

#### MISCELLANEOUS STONE

The following table gives data on certain types of dimension stone not included in the major groups already discussed. The principal varieties are mica schist, argillite, various light-color volcanic rocks, soapstone, and greenstone. The quantity sold in 1942 decreased 23 percent and the value 8 percent compared with 1941.

Miscellaneous varieties of stone (dimension stone) sold or used by producers in the United States in 1942, by States and uses

			Buil	ding	•				•
State	Active plants		gh and ssed	Ru	bble	Flag	ging	То	tal
		Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
Alabama California Florida Georgia Maryland Michigan New York North Carolina Ohio Pennsylvania Virginia Washington Undistributed	1 4 1 2 5 1 3 1 1 7 2 1	(1) 4,940 (1) (25,520 (1) (1) (1) 13,790	(1) \$14, 188 (1) (1) 40, 443 (1) (1) 770, 485	(1) 9, 370 	21, 936 (1) (1) (1) (1) (1) (1) (1) (1) (1) (1)	(¹) 460 	(1) \$2, 315 (1) (1) 8, 154	(1) 9,370 (1) 10,450 (1) 620 (1) 25,520 (1) (2) 22,170	(1)_ \$28, 894 (1) 38, 439 (1) 2, 676 (1) 40, 443 (1) 784, 128
Average unit value	29	<sup>3</sup> 44, 250	825, 116 \$18. 65	22, 270	58, 995 \$2, 65	<b>1</b> , 610	10, 469 \$6. 50	68, 130	894, 580 \$13. 13

<sup>1</sup> Included under "Undistributed."
2 Building stone (rough and dressed), approximately 536,450 cubic feet; flagging, approximately 20,140 cubic feet.

#### TRENDS IN USE OF DIMENSION STONE

Figure 1 shows graphically the history of production of dimension stone, by kinds, for a 27-year period. Dimension stone includes all classes of building stone, as well as memorial stone, paving blocks, curbing, and flagging. Limestone and granite are the leading varieties. All types of stone follow closely the general trends of national peacetime prosperity.

Figure 2 traces the history of production of all building stones and of the principal variety—limestone—in their relation to nonresidential building, the class of construction using stone most extensively. Stone is a dignified, substantial, and enduring building material that




FIGURE 1.—Sales of dimension stone in the United States, by kinds, 1916-42.




Figure 2.—Sales of all building stone and building limestone compared with nonresidential construction (public and private), 1915-42. Data on nonresidential building construction from Bureau of Foreign and Domestic Commerce.

STONE 1237

is used chiefly in permanent and relatively costly structures. Wars discourage the use of dimension stone. Although military needs demand enormous expansion of factory and housing facilities, natural stone finds little or no place in such types of construction. Similarly, Nation-wide depressions have sudden and serious effects on construction, upon which the prosperity of the building-stone industries depends. As indicated in figure 2, building limestone enjoyed an 8-year period of prosperity (1923–30) after the First World War. The industry sank to low levels during the depression and was just emerging from this dark period with the prospect of another era of wider sales when the Second World War wiped out the moderate gains of 1936 to 1939 and depressed the level of activity to a point lower than that of 1918.

#### NEW DEVELOPMENTS

Dimension stone occupies a rather subordinate position in the war program, and no new developments in use or in technique of manufacture are to be recorded. Stone-working activities have fallen to low levels, and at the same time an unprecedented demand has arisen for men and machines to make war equipment. This condition has influenced the versatile stone industry to accommodate its facilities and manpower to the more urgent needs. Producers of monumental granite near Barre, Vt., have established a War Work Division having machine shops adapted to manufacture of munitions. The marble industry centered near Proctor, Vt., and the granite industry at Cold Springs, Minn., have likewise diverted their machinery, power, and skilled personnel to making metal parts of war equipment. Many granite workers along the coast of Maine, skilled in woodcraft of the northern forests, heeded the call in 1942 for more ships and devoted their energies to making wooden barges. It is probable that other companies are engaged in similar activities of which we have no record.

Efforts were also made to expand the manufacture of useful byproducts. One Barre (Vt.) memorial stone company makes chicken grit from waste granite, thus aiding the expanding food program and simplifying the transportation of grit to New England poultry centers.

#### CRUSHED AND BROKEN STONE

Over 194,000,000 short tons of crushed and broken stone were sold in 1942, exclusive of that used for making cement and lime. Sales increased 7 percent in quantity and 8 percent in value compared with 1941. The average value at point of origin increased 1 cent a ton.

The following table of salient statistics shows the quantity and value of crushed and broken stone sold during 1941 and 1942 by uses. Detailed data on asphaltic stone and slate granules and flour are given in the chapters on Asphalt and Slate.

Crushed and broken stone sold or used by producers in the United States, 1941-42, by principal uses

		1941		1942				
Use	Short tons	Valt	16	Short tons	Value			
		Total	Average	Short tons	Total	Average		
Concrete and road metal	110, 192, 610 10, 771, 300 27, 436, 440	\$106, 985, 808 7, 536, 451 20, 069, 296	\$0.97 .70	107, 701, 010 17, 566, 640	\$105, 583, 801 10, 810, 977	\$0. 98 . 62		
Alkali works Riprap Agricultural	5, 888, 260 5, 152, 640 11, 909, 640	20, 009, 296 2, 721, 635 5, 226, 623 14, 395, 831	. 73 . 46 1. 01 1. 21	30, 262, 910 6, 350, 450 8, 763, 980 13, 745, 400	24, 152, 113 3, 005, 483 9, 779, 249	. 80 . 47 1. 12		
Refractory (ganister, mica schist, dolomite, soapstone) Asphalt filler Calcium carbide works	2, 254, 120 443, 480	3, 279, 104 1, 050, 927	1. 45 2. 37	2, 718, 090 439, 430	3, 999, 929 1, 026, 138	1, 24 1, 47 2, 34		
Sugar factories Glass factories Paper mills	468, 600 624, 450 385, 680 361, 830	343, 241 936, 874 578, 226 643, 124	.73 1.50 1.50 1.78	430, 600 625, 520 434, 080	399, 169 986, 210 656, 775	. 93 1. 58 1. 51		
Other uses	5, 271, 930	10, 174, 452	1. 93	435, 200 5, 063, 720	760, 332 10, 147, 006	1. 75 2. 00		
Portland cement (including "ce- ment rock")1	181, 160, 980 ì	173, 941, 592	.96	194, 537, 030	188, 300, 436	. 97		
Natural cement ("cement rock")1	42, 735, 000	(2)		47, 657, 000	- (2)			
Total stone	12, 159, 000 236, 055, 000	(2)		12, 208, 000 254, 402, 000	(2)			
Asphaltic stoneSlate granules and flour	654, 692 437, 670	2, 312, 227 3, 105, 800	3. 53 7. 10	935, 295 483, 740	3, 450, 979 3, 404, 416	3. 69 7. 04		

Value reported as cement in chapter on Cement.
 No value available for stone used in manufacture of cement and lime.
 Value reported as lime in chapter on Lime.

The following tables show the tonnage and value of stone used for concrete aggregate, road construction, and railroad ballast for a series of years and by States for 1942.

Concrete and road metal and railroad ballast sold or used by producers in the United States, 1938-42

Year	Concrete and	d road metal	Railroad	ballast	Total		
Short tons		Value	Short tons	Value	Short tons	Value	
1938	88, 787, 080 96, 894, 220 92, 814, 090 110, 192, 610 107, 701, 010	\$84, 212, 446 88, 988, 217 86, 331, 273 106, 985, 808 105, 583, 801	5, 975, 970 6, 996, 800 7, 454, 300 10, 771, 300 17, 566, 640	\$4, 554, 775 4, 970, 058 5, 231, 815 7, 536, 451 10, 810, 977	94, 763, 050 103, 891, 020 100, 268, 390 120, 963, 910 125, 267, 650	\$88, 767, 22 93, 958, 27 91, 563, 08 114, 522, 25 116, 394, 77	

The state of the s

Concrete and road metal and railroad ballast sold or used by producers in the United States in 1942, by States

	Concrete and	l road metal	Railroad	i ballast	Total			
State	Short tons	Value	Short tons	Value	Short tons	Value		
Alabama	1 818, 600	1 \$941, 403	8, 490	\$4,076	1 827, 090	1 \$945, 479		
Arizona	1 110, 750	1 152, 647			1 110, 750	1 152, 64		
Arkansas	1, 429, 950	1, 588, 929	436.070	312, 240	1,866,020	1, 901, 16		
California	7, 563, 300	5, 074, 009	1 274, 590	1 91, 179	1 7, 837, 890	1 5, 165, 18		
Colorado	247, 370	194, 416	(2)	(2)	1 247, 370	1 194, 41		
Connecticut	1 1, 316, 340	1 1, 313, 448	86, 260	77, 691	1 1, 402, 600	1 1, 391, 13		
Delaware	(2)	(2)			(2)	(2)		
Florida	1 5, 430, 920	1 4, 674, 967	183, 960	141, 665	1 5, 614, 880	1 4, 816, 63		
Georgia	2,091,620	2, 406, 067	91, 190	85, 052	2, 182, 810	2, 491, 11		
Hawaii	(2) 459, 390	(2) 573, 162	(2)	(2)	(2) 459, 390	<sup>(2)</sup> 573, 16		
Idaho	8, 674, 670	7, 458, 575	863, 230	688, 591	9, 537, 900	8, 147, 16		
Illinois Indiana	1 4, 736, 890	1 4, 197, 690	448, 400	362, 886	1 5, 185, 290	1 4, 560, 57		
Iowa	3, 031, 540	3, 192, 268	131, 990	63, 017	3, 163, 530	3, 255, 28		
Kansas	1 1, 891, 540	1 2, 184, 517	294, 230	227, 205	1 2, 185, 770	1 2, 411, 72		
Kentucky	1 4, 154, 430	1 4, 013, 844	501, 550	334, 673	1 4, 655, 980	1 4, 348, 51		
Louisiana	(2)	(2)	001,000	502,010	2, 000, 000	(2)		
Maine	46,040	62, 855			46,040	62, 85		
Maryland	822, 540	946, 158	156, 240	176, 853	978, 780	1, 123, 01		
Massachusetts	1, 225, 330	1, 456, 453	236, 200	218, 156	1, 461, 530	1, 674, 60		
Michigan	1, 918, 210	1, 205, 765	141, 370	112, 723	2, 051, 580	1, 318, 48		
Minnesota	1 867, 410	1 775, 739	347, 740	331,650	1 1, 215, 150	1 1, 107, 38		
Missouri	6, 140, 960	5, 932, 834	1, 594, 920	306, 980	7, 735, 880	6, 239, 81		
Montana	s 196, 110	122, 423	(2)	(2)	1 196, 110	1 122, 42		
Nebraska	107, 320	114, 115			107, 320	114, 11		
Nevada	1 50, 820	1 72, 415			1 50, 820	1 72, 41.		
New Hampshire	179, 150	267, 942			179, 150	267, 94		
New Jersey	2, 832, 850	2, 892, 354	172, 570	182, 509	3, 005, 420	3, 074, 86		
New Mexico	(2)	(2)	(2)	(2)	1 8, 371, 800	(2) 1 8, 353, 54		
New York	1 7, 094, 890	1 7, 468, 341	1 1, 276, 910	1 885, 203				
North Carolina	1 2, 339, 210	1 2, 797, 812	1 307, 390	1 285, 238	1 2, 646, 600	1 3, 083, 05 (2)		
North Dakota	1 0 479 050	1 = 7 = 200	1 056 000	827, 185	1 7, 530, 750	1 6, 582, 507		
Ohio	1 6, 473, 950 1 3, 034, 020	1 5, 755, 322 1 2, 148, 450	1, 056, 800 2, 796, 130	547, 078	1 5, 830, 150	1 2, 695, 52		
Oklahoma Oregon	2, 508, 870	2, 492, 564	4, 290	3, 630	2, 513, 160	2, 496, 19		
Pennsylvania	7, 970, 300	8, 843, 516	1, 381, 540	1, 227, 829	9, 351, 840	10, 071, 34		
Puerto Rico	(2)	(2)	(2)	(2)	(2)	(2)		
Rhode Island	181, 670	166, 676		( )	181,670	166, 67		
South Carolina	1, 483, 990	1, 733, 913	425, 840	382, 875	1, 909, 830	2, 116, 78		
South Dakota	609, 420	839, 296	120,010	00-, 0.0	609, 420	839, 29		
Tennessee	4, 928, 140	5, 464, 542	662,000	471, 210	5, 590, 140	5, 935, 75		
Texas	2, 353, 420	2, 420, 909	933, 930	421, 812	3, 287, 350	2, 842, 72		
Utah	(2)	(2)			(2)	(2)		
Vermont	26, 310	44,090			26, 310	44,09		
Virginia	3, 757, 900	3, 818, 543	1 900, 910	1 755, 940	1 4, 658, 810	1 4, 574, 48		
Washington	1 1, 357, 550	1 1, 100, 399	191, 790	116, 171	1 1, 549, 340	1 1. 216, 57		
West Virginia	î 919, 870	1 983, 622	382, 370	321, 601	1 1, 302, 240	1 1, 305, 22		
Wisconsin	2, 445, 750	2, 062, 884	444, 810	413, 531	2, 890, 560	2, 476, 41		
Wyoming	(2)	(3)	(2)	(2)	4 704 620	(3) e 069 45		
Undistributed	3, 871, 700	5, 627, 927	832, 930	434, 528	4, 704, 630	6, 062, 45		
4.1.	107, 701, 010	105, 583, 801	17, 566, 640	10, 810, 977	125, 267, 650	116, 394, 77		

<sup>&</sup>lt;sup>1</sup> To avoid disclosing confidential information certain totals are somewhat incomplete, the figures not included being combined under "Undistributed."

<sup>3</sup> Included under "Undistributed."

### COMMERCIAL AND NONCOMMERCIAL OPERATIONS

The following table shows the production of crushed stone for concrete and road metal and railroad ballast during recent years by Government agencies of various kinds contrasted with that by commercial enterprises. Production by commercial companies increased 27 percent in 1942 compared with 1941, whereas production by Government agencies declined 55 percent. Eighty-eight percent of the total production was made by commercial companies. The large decline in noncommercial output reflects the curtailment of makework enterprises established to combat the depression.

Concrete and road metal and railroad ballast sold or used by commercial and noncommercial operators in the United States, 1938-42

[Figures for "noncommercial operations" represent tonnages reported by States, counties, municipalities, and other Government agencies, produced either by themselves or by contractors expressly for their consumption, often with publicly owned equipment; they do not include purchases from commercial producers. Figures for "commercial operations" represent tonnages reported by all other producers]

	Comi	mercial	operation	s	Noncor	nmercia	Total			
Year	Short tons	Average value per ton	Percent of change in quan- tity from preced- ing year		Short tons		Percent of change in quan- tity from preced- ing year	Per-	Short tons	Percent of change in quan- tity from preced- ing year
1938 1939 1940 1941 1942	60, 254, 170 59, 516, 270 63, 203, 240 86, 360, 120 109, 818, 570	\$0.88 .86 .87 .91 .91	$ \begin{array}{ c c c } -3.3 \\ -1.2 \\ +6.2 \\ +36.6 \\ +27.2 \end{array} $	63. 6 57. 3 63. 0 71. 4 87. 7	34, 508, 880 44, 374, 750 37, 065, 150 34, 603, 790 15, 449, 080	\$1.04 .97 1:02 1.04 1.05	+32. 1 +28. 6 -16. 5 -6. 6 -55. 4	37. 0 28. 6	94, 763, 050 103, 891, 020 100, 268, 390 120, 963, 910 125, 267, 650	+7. 2 +9. 6 -3. 5 -20. 6 +3. 6

#### SIZE OF PLANTS

Presented herein for the first time is an analysis of production by size of plant. The determinations are based upon 1941 figures. The largest group of plants, comprising 46 percent of the total, includes those ranging in output from 1,000 to 25,000 tons a year. The second-largest group includes plants that produce 25,000 to 50,000 tons a year. These two groups, although comprising 61 percent of the total number of plants, produce less than 12 percent of the total output. The third group in importance, based upon the number of plants, includes those producing 100,000 to 200,000 tons a year; this group is second in importance in production, for it contributes 15 percent of total output. Plants producing 900,000 tons and over a year, although only 19 in number, furnish more than 23 percent of the total production. The accompanying table gives details of production by size groups.

Number and production of commercial crushed-stone plants, by sizes of output, 1941 1

Range of output	Number of plants	Total produc- tion of plants (short tons)	Percent of total	Cumulative total (short tons)
Less than 1,000 tons. 1,000 to 25,000. 25,000 to 50,000. 50,000 to 75,000. 75,000 to 100,000. 100,000 to 200,000. 200,000 to 300,000. 300,000 to 400,000. 400,000 to 500,000. 500,000 to 700,000. 600,000 to 700,000. 700,000 to 800,000. 800,000 to 900,000. 900,000 to 900,000.	141 805 254 141 82 147 58 39 29 7 5 6 4	99, 460 7, 639, 860 8, 893, 690 8, 655, 220 7, 125, 430 21, 549, 890 14, 225, 700 13, 556, 340 13, 139, 480 3, 850, 070 3, 243, 550 4, 494, 440 3, 367, 900 33, 186, 870	0. 07 5. 34 6. 22 6. 05 4. 98 15. 07 9. 94 9. 19 2. 69 2. 27 3. 14 2. 35 23. 20	99, 460 7, 739, 320 16, 633, 010 25, 288, 230 32, 413, 660 53, 963, 550 81, 755, 590 94, 895, 070 98, 745, 140 101, 988, 690 106, 483, 130 109, 851, 030 143, 037, 900
Totāl	1,737	143, 037, 900	100.00	143, 037, 900

<sup>1</sup> Exclusive of marble, which is primarily a dimension-stone industry.

### METHODS OF TRANSPORTATION

The following table shows the quantities of concrete and road metal conveyed during 1941 and 1942 by each of the principal methods of transportation. The general trend in mode of transport for the past 10 years has been toward wider use of trucks at the expense of railroads. In 1942, for the first time, this trend was reversed, and truck haulage declined from 65 percent of the total commercial output in 1941 to only 55 percent in 1942; conversely, rail tonnage increased from 24 to 30 percent of the total. This condition doubtless reflects the restrictions in use of rubber and gasoline prevalent in 1942.

Concrete and road metal sold or used by commercial producers in the United States, 1941-42, by methods of transportation <sup>1</sup>

•	1941		1942		
Method of transportation	Short tons	Percent of total	Short tons	Percent of total	
Truck	49, 107, 430 18, 047, 780 4, 690, 770 3, 742, 840	65. 0 23. 9 6. 2 4. 9	50, 830, 270 27, 932, 080 4, 311, 930 9, 177, 650	55. 1 30. 3 4. 7 9. 9	
Unspecimous	75, 588, 820	100.0	92, 251, 930	100.	

<sup>&</sup>lt;sup>1</sup> For practical purposes the entire output of noncommercial operations commonly is moved by truck. Including noncommercial production, crushed stone for concrete and road metal moved as follows—1941: Truck 76 percent, rail 16 percent, waterway 4 percent, and unspecified 4 percent; 1942: Truck 62 percent, rail 26 percent, water 4 percent, and unspecified 8 percent.

GRANITE

Granite (crushed and broken stone) sold or used by producers in the United States in 1942, by States and uses

	Ri	prap		Crushe	ed stone	, i sa e e e e e e e e e e e e e e e e e e	Other uses 1				
State			Concrete and road metal		Railroac	Railroad ballast		uses 1	To	Total	
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	
California Colorado Connecticut	1, 040, 370 (2) (2)	\$1,389,960 (2) (2)	1, 233, 260	\$749, 924 (2)	89, 010	\$43,390	29, 830	\$13, 888	2, 392, 470 122, 280	\$2, 197, 162 79, 500	
Delaware. Georgia Idaho	962, 930	(2) 745, 564	(2) 1, 909, 050	(2) 2, 219, 661	91, 190	85, 052	(2) (2) 203, 050	(2) (2) 214, 409	(2) (2) (3) (3) (3) (4) (5)	(2) (2) (3) 3, 264, 686	
Maryland Massachusetts	(2) (2) 8, 210	(2) (2) (2) (2)	(2)	(2)	(2)	(2)			9, 120 110, 940	17, 465 217, 073	
Minnesota Missouri Montana	94, 480 400 1, 840	9, 979 49, 240 500 845	334, 360 21, 400	483, 615 40, 400	60, 950	60, 278	11, 370	15, 361	353, 940 176, 830 400	508, 955 149, 918 500	
New Jersey	(2) 12, 340	(²) 9, 895	113, 020 179, 150 (2)	62, 058 267, 942 (2)	(2) 44, 320	( <sup>2</sup> ) 35, 454	(2)	(2)	114, 860 230, 150 (2)	62, 903 319, 143 (2)	
Oklahoma North Dakota	219, 910 6, 650	219, 737 6, 644	202, 850 2, 011, 400 41, 530	182, 328 2, 357, 328 47, 649	307, 390	35, 454 285, 238	12, 810 18, 450	5, 843 101, 913	272, 320 2, 557, 150 48, 180	233, 520 2, 964, 216 54, 293	
Puerto Rico Rhode Island	12, 360	13, 380	333, 220 (2)	(2) 482, 740 (2) (2)			560	2, 444	(2) 346, 140 (2)	(2) 498, 564 (2)	
South Dakota Tennessee	35, 270 26, 380	39, 864 26, 803	1, 353, 880 226, 640 (2)	1, 576, 955 298, 010 (2)	425, 840	382, 875	12, 520	5, 150	1, 827, 510 253, 020	(2) 2, 004, 844 324, 813	
Virginia Washington	280 (2) (2)	(2) (3)	889, 190	1, 022, 776	187, 640	199, 562	(2)	(3) (2)	(2) 280 1, 132, 170	(2) 496 1, 264, 735	
Wisconsin	3, 170 131, 580	2, 337 219, 786	79, 640 (2) 465, 840	40, 527 (2) 586, 139	23. 850	32, 241	2, 180 71, 050	5, 732	24, 440 84, 990 (²)	28, 090 48, 596 (2) 474, 289	
Average unit value	2, 556, 170	2, 735, 030 \$1. 07	9, 394, 430	10, 418, 052 \$1, 11	1, 230, 190	1, 124, 090 \$0, 91	361, 820	71, 849 436, 589 \$1, 21	319, 200 13, 542, 610	14, 713, 761 \$1. 09	

<sup>&</sup>lt;sup>1</sup> Includes stone used for artificial stone, fertilizer filler, poultry grit, spalls, stone sand, and terrazzo.

Included under "Undistributed."

STONE 1243

Sales of crushed and broken granite were about the same in 1942 as in 1941, but the value was 4 percent greater owing to an increase in sales value from \$1.05 to \$1.09 a ton. Production of riprap was unusually high, but on the other hand sales of concrete aggregate and stone for highway construction dropped about 1 million tons.

The number of individual operations supplying noncommercial crushed stone cannot be determined with any degree of accuracy from the reports submitted. Therefore, in the accompanying tables covering granite and other kinds of crushed and broken stone, the number of active plants is not given. For many years before 1939, when noncommercial production had less importance, such figures appeared in the tables.

# BASALT AND RELATED ROCKS (TRAP ROCK)

The dark igneous rocks, basalt, gabbro, and diorite, known commercially as trap rock, are used widely for highway construction and concrete aggregate. Sales of crushed and broken trap rock were 2 percent less in 1942 than in 1941, and the value was 13 percent higher. The value per ton increased from \$1.04 to \$1.19.

Sales of riprap, which had declined in 1941, gained 57 percent in 1942. Stone for concrete aggregate and road metal declined moderately, but railroad-ballast sales increased substantially. The latter condition reflected the increasing care devoted to roadbeds at a time

when rail traffic was exceptionally heavy.

# Basalt and related rocks (trap rock) (crushed and broken stone) sold or used by producers in the United States in 1942, by States and uses

	D:-			Crushe	d stone		Other		То	401
State	Riprap		Concrete and road metal		Railroad ballast		O vinor uses			
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
ArizonaArkansas			(2) (2)	(2)					(2)	(2) (2)
CaliforniaColorado		\$615,092	1, 284, 730 89, 210	\$1, 264, 658 90, 900	5, 670	\$5, 683	51, 510	\$47, 981	1, 841, 920 89, 210	\$1, 933, 414 90, 900
Connecticut——————————————————————————————————	(2)	86, 319 (2)	1, 316, 340 (2)	1, 313, 448 (2)	86, 260 (²)	77, 691 (²)			1, 497, 600 (2)	1, 477, 458 (2) 438, 413
IdahoMaine	1, 500	700	345, 060 33, 990	437, 713 41, 100					346, 560 33, 990	41, 100
Maryland	(2) (2) 320	(2) (2) 316	809, 670 98, 300	(2) 871, 213 145, 002	(2) 236, 200 350	(2) 218, 156 350	(2)	(2)	424, 950 1, 091, 010 98, 970	545, 072 1, 168, 994 145, 668
Minnesota	(2) (2)	(2) (2)	(2)	(2)	(2)	(2)			(2)	(2)
New York	117, 580	166,001	2, 572, 700 733, 580	2, 826, 272 933, 110	151, 940 244, 490	154, 506 306, 145	84, 640	66, 626	2, 926, 860 978, 070	3, 213, 405 1, 239, 255 72, 203
North Carolina Oregon Pennsylvania	13, 120 4, 690	3, 357 5, 855	42, 120 2, 316, 680 1, 050, 660	72, 203 2, 327, 934 1, 223, 475	4, 290 317, 170	236, 778			42, 120 2, 334, 090 1, 372, 520	72, 203 2, 334, 921 1, 466, 108
Puerto Rico			(2)	(2)	(2)	(2)			(2)	(2)
Texas. Virginia. Washington.	(2)	(²) 177, 463	(2) (2) 1, 322, 090	(2) (2) 1, 081, 596	(2) (2) 191, 790	(2) (2) 116, 171			310, 920 1, 728, 650	335, 674 1, 375, 230
WisconsinUndistributed	25, 790	23, 838	2, 873, 860	4, 908, 972	<sup>(2)</sup> 280, 740	<sup>(2)</sup> 270, 517	(2) 97, 090	(2) 868, 651	2, 496, 470	5, 111, 607
Average unit value	972, 780	1, 078, 941 \$1. 11	14, 888, 990	17, 537, 596 \$1. 18	1, 518, 900	1, 389, 627 \$0. 91	233, 240	983, 258 \$4. 22	17, 613, 910	20, 999, 422 \$1. 19

<sup>&</sup>lt;sup>1</sup> Includes stone sold for fill material, roofing granules, and unspecified uses.

Included under "Undistributed."

#### MARBLE

Waste material from most marble quarries and mills in the United States consists of relatively pure calcium carbonate and therefore is interchangeable with high-calcium limestone for various uses. As many blocks quarried are structurally defective and as a considerable share of the good blocks is cut away in marble dressing, large quantities of waste material accumulate. Marble producers are active, therefore, in seeking profitable outlets for such waste. Some of them manufacture finely pulverized, relatively high-priced products, such as whiting and fillers. Others prepare it for terrazzo, stucco, or agricultural limestone. The rough blocks may be sold for riprap or may be crushed for use as roadstone or concrete aggregate. This diversity in preparation and use explains the great variation in price obtained in different States as indicated in the accompanying table.

Marble (crushed and broken stone) sold by producers in the United States in 1942, by
States 1

State	Active plants	Short tons	Value	State	Active plants	Short tons	Value
Alabama California Georgia Maryland Massachusetts Missouri New York Tennessee	2 3 1 1 1 1 1 5	(2) 2, 940 10, 000 1, 700 3, 500 (2) 21, 900 23, 240	(2) \$25, 950 10, 431 19, 349 4, 428 (2) 140, 144 25, 153	Texas	2 1 2 4 2 24	6, 150 5, 130 3, 830 (2) 42, 520 120, 910	\$41, 392 42, 828 16, 113 (2) 132, 688 458, 478 \$3. 79

<sup>&</sup>lt;sup>1</sup> Includes artificial stone, crushed stone, flux, mineral food, poultry grit, riprap, spalls, stucco, terrazzo, whiting (excluding marble whiting made by companies that purchase their marble).

<sup>2</sup> Included under "Undistributed."

#### LIMESTONE

Limestone occurs in every State, and sales were reported to the Bureau of Mines from 44 of them. Because of its wide occurrence it is, in many areas, the most convenient kind of stone for highway or building construction and railroad ballast. The over-all cost of quarrying and crushing limestone is generally lower than that of the harder rocks. Limestone is an essential raw material for many metallurigical, chemical, and processing industries for which no other kinds of stone can be substituted. As a result of these various favorable conditions, limestone is by far the most widely used type of stone in the United States. In 1942 limestone constituted 73 percent of all crushed and broken stone sold (excluding that used for making cement and lime).

Sales in 1942 were 7 percent higher in quantity and 10 percent in value than in 1941. Riprap sales made small gains, and the value per ton increased from 95 cents to \$1.09. Fluxing-stone sales, which reached an all-time high of more than 30 million tons, reflect the unprecedented iron-furnace activity in 1942. There was no substantial change in limestone sold for concrete aggregate and road building, but the increase in railroad-ballast sales was comparable with that of basalt and for the same reason. The 15-percent increase in sales of agricultural limestone relates directly to the stimulation of

crop growing that characterized 1942.

# Limestone (crushed and broken stone) sold or used by producers in the United States in 1942, by States and uses

				•		Crushe	d stone							
State	Rip	rap	Fluxin	g stone	Concrete		Railroad	ballast	Agric	ılture	Otl	he <b>r</b>	То	tal
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
AlabamaArizona	17, 080	\$28, 507	1, 912, 380 23, 680	\$1, 614, 240 14, 298	818, 600 64, 190	\$941, 403 89, 152	8, 490	\$4, 076	181, 700	\$217, 348	91, 640	<b>\$542, 287</b>	3, 029, 890 87, 870	\$3, 347, 861 103, 450
Arkansas California Colorado	(1) (1) (1)	(1) (1)	(1) 54, 560	(1) 96, 207	584, 900 433, 830	564, 801	(1)	(1) (1)	(1)	(1) (1)	(1) 278, 310 185, 300	(1) 755, 556 177, 658	660, 670 1, 056, 740 573, 720	713, 482 1, 441, 253 399, 697
Connecticut Florida Georgia	3, 100	1, 327	(i)	(1) (1) (1)	(1) 5, 430, 920 182, 570	(1) 4, 674, 967 186, 406	183, 960	141, 665	36, 190 51, 720 74, 070	110, 974 176, 877 194, 873	(1) 893, 720 (1)	(1)	47, 480	145, 759 5, 670, 590 569, 280
Hawaii Idaho Illinois		91, 435	498, 150	458, 273	(1)	(1) 7, 442, 875		688, 591	7		(1) 645, 940	(1) 886, 267	(1) (1) 14, 021, 490	(1)
Indiana IowaKansas	50, 230 71, 010	38, 285 63, 773 60, 000	15, 530 25, 120	9, 518	4, 736, 890 3, 031, 540 1, 629, 760	4, 197, 690 3, 192, 268 2, 146, 000	448, 400 131, 990 189, 500	362, 886 63, 017 213, 748	965, 720 1, 171, 890 67, 430	948, 601 1, 293, 367 70, 055	128, 130 37, 770 (1)	115, 658 208, 691 (1)	6, 344, 900 4, 469, 320 1, 979, 180	5, 672, 638 4, 845, 154 2, 621, 200
Kentucky Louisiana Maine			61, 260	89, 129	4, 154, 430 (1) 340	4, 013, 844 (1) 516			22, 960	72, 730	12, 040 (1) 37, 380	(1) 65, <b>3</b> 99	(¹) 121, 940	
Maryland Massachusetts Michigan		(1) 6, 241	16, 870 9, 259, 080	25, 763 5, 299, 088	1, 817, 530	1, 056, 005	36, 240 141, 020		152, 850	184, 824	(1) 24, 750 4, 422, 390	2, 390, 657	610, 650 194, 470 15, 884, 930	587, 224 9, 049, 188
Minnesota	20, 480 152, 180	18, 249 167, 993	(1)	(1)	846, 010	735, 339 5, 670, 847	84, 370 (1)	(1) 81, 362 (1)	l	1, 112, 758	25, 620 246, 680 41, 860	61, 998 472, 707 66, 420	1, 241, 490 6, 665, 760 177, 670	1, 208, 272 7, 523, 705 180, 082
Nebraska Nevada New Jersey	(1)	(1)	(1) (1)	(1)	107, 320 (1) 14, 520	(1)			(1)	(1) (1)	67, 530 (1) (1)	377, 963 (1) (1)	267, 020 (1), 197, 960	(1) 487, 678
New Mexico New York North Carolina	371, 880	<sup>(1)</sup> 538, 714			6, 053, 390 179, 720	6, 231, 115 234, 908	(1) 988, 100	(1) 543, 604 (1)			1, 677, 230	1, 114, 157	9, 564, 930 196, 630	9, 417, 729 258, 761
Ohio Oklahoma Oregon	30,040 54,210	29, 616 56, 745	5, 091, 320 (¹)	3, 562, 637 (¹)	6, 473, 450	5, 754, 522 1, 933, 689	1, 056, 800	827, 185	1, 418, 370	1, 533, 276 42, 045	453, 280 (1)	(1)	14, 523, 260 2, 288, 440 53, 900	12, 348, 690 2, 251, 029
Pennsylvania Puerto Rico Rhode Island	39, 970		(1)	(1)	5, 944, 580	6, 415, 878	823, 230 (¹)	732, 313 (¹)		1, 671, 390	1, 062, 320 (1) (1)	1, 862, 832 (1) (1)	19, 023, 500 (1) (1)	
South Carolina					(1) 276,000	399, 025			(1)	(1) (1)	15, 100		291, 300	(1) 427, 425

Tennessee Texas	641, 450 47, 250 (¹)		66, 940 (1) 167, 320	68, 251 (1) 137, 171	2, 118, 760	5, 447, 542 2, 236, 190				1, 059, 629 (¹)	111, 280 285, 960 58, 870	326, 435	3, 304, 440	7, 867, 099 2, 954, 244 255, 559 779, 460
Virginia Washington	28, 670	42, 194	688, 490 4, 720	695, 393 3, 576		2, 401, 135 4, 568		512, 253			756, 460 133, 950	817, 507 284, 733	5, 368, 440	5, 263, 208 347, 855
West Virginia Wisconsin Wyoming	(1) 19, 620 (1)	(1) 18, 908 (1)	1, 160, 060	3, 576 959, 524 40, 922 (1)	499, 990 2, 313, 410	602, 761	382, 370	321, 601 409, 794	120, 030	183, 641	(1)	(1)	2, 563, 440	2, 469, 986 3, 712, 451 203, 699
Undistributed	366, 810	372, 466	592, 550	415, 540	1, 597, 610	1, 396, 570	865, 620	553, 948	298, 460	585, 712	1, 453, 960	2, 563, 222	2, 709, 260	2, 157, 568
Average unit value	2, 371, 720	2, 596, 444 \$1. 09			72, 803, 290	70, 854, 215 \$0. 97		6, 923, 225 \$0. 72		16, 993, 254 \$1. 24			142, 024, 630	136, 433, 540 \$0. 96

<sup>&</sup>lt;sup>1</sup> Included under "Undistributed."

Limestone (crushed and broken stone) sold or used by producers in the United States for miscellaneous uses, 1941-42

Use	194	1	1942			
USO	Short tons	Value	Short tons	Value		
Alkali works	5, 888, 260	\$2,721,635	6, 350, 450	\$3, 005, 483		
Calcium carbide works	468, 600	343, 241	430, 600	399, 169		
Coal-mine dusting	136, 180	388, 962	193, 260	491, 819		
Filter (not whiting substitute):	,	,	,	101,010		
Asphalt	443, 480	1, 050, 927	439, 430	1, 026, 138		
Fertilizer	301, 650	548, 104	226, 910	407, 301		
Other	68, 980	295, 713	107, 760	379, 948		
riter beds	32, 950	41, 787	66, 310	111, 417		
Glass factories	385, 680	578, 226	434, 080	656, 775		
Limestone sand	877, 730	812, 517	484, 810	369, 408		
Limestone whiting 1	417, 750	2, 421, 609	326, 930	2, 277, 835		
Magnesia works (dolomite)	105, 670	136, 180	117, 650	151, 756		
Mineral food Mineral (rock) wool	115, 400	546, 784	169, 880	792, 949		
Mineral (rock) wool	115, 760	93, 167	119, 620	106, 985		
Paper mills	361, 830	643, 124	435, 200	760, 332		
Poultry grit	62, 070	351, 809	62, 620	371, 221		
Refractory (dead-burned dolomite)	980, 190	729, 792	1, 354, 090	1, 197, 386		
Road base	575, 130	441, 355	931, 680	740, 557		
Stucco, terrazzo, and artificial stone	25, 840	166, 021	17, 890	123, 643		
Sugar factories	624, 450	936, 874	625, 520	986, 210		
Other uses 2	156, 250	287, 933	213, 980	317, 478		
Use unspecified	159, 980	252, 972	91, 230	245, 279		
	12, 303, 830	13, 788, 732	13, 199, 900	14, 919, 089		

<sup>&</sup>lt;sup>1</sup> Includes stone for filler for calcimine, caulking compounds, chewing gum, cosmetics, explosives, flavoring extracts, imitation leather, linoleum, paint, paper, parting compounds, phonograph records, plastics, pottery, printing ink, putty, regrinding, roofing, rubber, sealing wax, tile, tooth powder, wire, and unspecified uses.

Dolomite (calcium-magnesium carbonate), which occurs extensively in the United States, is attaining increasing commercial importance. Its new use as a source of magnesium metal, plus growing demands for refractory magnesia, one of its derivatives, led the Bureau of Mines to make a comprehensive survey of United States resources of this important rock. Data on high-grade dolomite deposits assembled from all available published sources were supplemented by additional information secured from State geological surveys, geologists, and This report covers the occurrences by geographic mining engineers. areas and by States. The extent and thickness of the deposits, altitude of beds, accessibility, workability, and composition are An important feature of the paper is a series of tables comprising about 1,000 representative analyses of dolomites from all parts of the country. A map shows the location of the deposits.

The record-breaking demand for refractories to maintain maximum operation of innumerable furnaces turning out metal for war munitions resulted in so many calls for information on special types of heat-resisting products that the Bureau prepared a report <sup>2</sup> dealing with all recent developments in the refractories for which dolomite is used as raw material.

Sales of dolomite and its primary product of calcination—dolomitic lime—for certain special uses are covered in the following table:

uses.

Includes stone for acid neutralization, carbon dioxide, ceramics, chemicals (unspecified), concrete blocks and pipes, dye, foundry facings, motion-picture snow, oil-well drilling, rayon, rice milling, spalls, and spray.

Weitz, John H., High-Grade Dolomite Deposits of the United States: Bureau of Mines Inf. Circ. 7226, 1942.
 Schallis, Alvin, Dolomite-Base Refractories: Bureau of Mines Inf. Circ. 7227, 1942, 11 pp.

Dolomite and dolomitic lime sold or used by producers in the United States for specified purposes, 1941-42

	1941	1942
Dolomite for—		
Basic magnesium carbonate: Short tons.	105, 670	117, 650
Value  Dead-burned dolomite or refractory stone:	\$136, 180	\$151,756
Short tons	980, 190	1, 354, 090
ValueDolomitic lime for—	\$729, 792	\$1, 197, 386
Refractory (dead-burned dolomite):	1, 069, 887	1 000 957
Short tonsValue	\$9, 111, 172	1, 229, 357 \$10, 817, 634
Paper mills: Short tons	78,000	85, 000
Value	\$551,000	\$604,000
Total (calculated as raw stone)short tons	3, 382, 000	4, 100, 000

Fluxing limestone has attained such importance that the Bureau of Mines for the first time has separated the figures by principal uses, as indicated in the accompanying table.

Sales of fluxing limestone, 1938-42, by uses

Blast furnaces			hearth ants		ther lters <sup>1</sup>		metal- ical <sup>2</sup>	Total			
Year	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	
1938	13, 115, 580 15, 611, 720 20, 244, 510	\$4, 455, 693 9, 505, 807 10, 638, 341 14, 832, 938 18, 523, 158	3, 471, 570 6, 500, 680 6, 332, 210	2, 638, 935 4, 462, 852 4, 469, 838	522, 330 342, 240 481, 100	331, 969 278, 726 398, 839	162, 080 402, 270 374, 700	142, 227 358, 968 362, 544	9, 692, 130 17, 271, 560 22, 856, 910 27, 432, 520 30, 259, 250	12, 618, 938 15, 738, 88 20, 064, 159	

<sup>1</sup> Includes flux for copper, gold, lead, zinc, and unspecified smelters.
2 Includes flux for foundries and for cupola and electric furnaces.

Limestone is quarried not only for use raw but also for manufacture into cement and lime. The large and important industries manufacturing these products are covered in separate chapters of the Yearbook. It is of interest, however, to show in one table, as follows, the total tonnage of limestone consumed for all purposes.

Limestone sold or used for all purposes in the United States, 1940-42, in short tons

Use	1940	1941	1942
Limestone (as given in this report) (approximate)	112, 658, 000	133, 164, 000	142, 488, 000
	34, 041, 000	42, 735, 000	47, 657, 000
	9, 774, 000	12, 159, 000	12, 208, 000
	156, 473, 000	188, 058, 000	202, 353, 000

Reported in terms of cement in chapter on Cement.
 Reported in terms of lime in chapter on Lime.

#### SANDSTONE

Sales of crushed sandstone were 13 percent lower in quantity and 20 percent lower in value in 1942 than in 1941. Ganister, the principal raw material of silica brick used extensively to line openhearth steel furnaces, was produced in larger quantities in 1942 than in any previous year. The output was 2 percent greater than the former high of 1917.

Sandstone (crushed and broken stone) sold or used by producers in the United States in 1942, by States and uses

	Refracto	ory stone	Di-	Riprap Crushed stone				Other uses 1				
State	(gan	ister)	Kı	гар		and road	Railroad	l ballast	Other	uses 1	То	tal
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
AlabamaArizona	(2)	(2)	(2)	(2)	(3)	(²)					66, 670	\$69, 388 (2)
Arkansas California Colorado Idaho	22, 980	\$68, 239 34, 456	20, 760 12, 120	\$24, 404 23, 027	353, 690 887, 870 2, 120 (²)	\$382, 750 651, 725 2, 387 (2)	1,000	\$501	383, 490	\$93, 186	353, 690 1, 309, 470 37, 220	382, 750 838, 055 59, 870
Kansas Kentucky	(2)	(2)	(2) (2)	(2) (2)	(2)	(2)					2, 950 207, 490 (2)	(2) 9, 376 257, 056 (2)
Maryland Michigan Minnesota Montana			1, 400	(2) 1, 257	(2)	(2)				(2)	(2) (2) (2) 1, 400	(2) (2) 1, 257
Nevada New York North Carolina		(2)	(2) (2) (2) (2)	(2) (2) (2)	(2) 105, 070 (2)	(2) 121, 788 (2)			8, 500		91, 030 (2) 113, 570	43, 189 (2) 132, 413
Ohio Oklahoma Oregon	96, 970	483, 765	142, 260 (2)	207, 779 (²)	(2) (2) (2)	(2) (2) (2)			(2)	(2)	(2) 239, 730 (2) 128, 610	(2) 692, 344 (2) 128, 130
Pennsylvania South Dakota Tennessee	(2)	1, 398, 188 (2) (2)	183, 580 22, 940 (2)	185, 933 26, 833 (2) (2)	546, 780 84, 950	595, 075 118, 664	241, 140	258, 738	343, 650 (2)	271, 855 (2)	2, 079, 290 133, 430 (2)	2, 709, 789 194, 833 (²)
TexasUtahVermont.	(2)	(2)	(2)	(2)	(2) 8, 820	(2) 14, 545					2, 190 (2) 8, 820	1, 957 (²) 14, 545
Virginia Washington		<b>32, 3</b> 03	(2)	(2) 76	55, 560	31, 562	66, 690	44, 125	18, 060	8, 608	166, 300 (2)	116, 674 (2)
West Virginia Wisconsin Wyoming	<sup>(2)</sup> 230, 040	(2) 348, 306	55, 860 (2) (2)	114, 718 (2) (2)	419, 880 (2)	380, 861 (²)			(2) (2)	(2) (2)	605, 090 395, 440 (2)	673, 002 747, 821
Undistributed	166, 940	259, 070	636, 930	527, 394	331, 200	346, 634			209, 840	436, 764	525, 680	(2) 434, 492
Average unit value	1, 329, 260	2, 624, 327 \$1. 97	1, 076, 000	1, 111, 421 \$1. 03	2, 790, 440	2, 646, 791 \$0. 95	308, 830	303, 364 \$0. 98	963, 540	821, 038 \$0. 85	6, 468, 070	7, 506, 941 \$1.16

<sup>1</sup> Includes sandstone for chemical use, fill material, filter stone, poultry grit, road base, rock wool, roofing granules, and stone sand. 2 Included under "Undistributed."

### MISCELLANEOUS STONE

Crushed and broken stone, other than the five principal varieties already discussed, includes light-color volcanic rocks, schists, boulders from river beds, serpentine, and flint. The following table shows sales of stone of these types, by States and uses, in 1942; such sales increased 50 percent in quantity and 8 percent in value over 1941.

# Miscellaneous varieties of stone (crushed and broken stone) sold or used by producers in the United States in 1942, by States and uses

	Rip	Riprap Crushed stone		The second second	Other	ses <sup>1</sup> Total				
State			Concrete and	l road metal	Railroad	ballast	Short tons	Value	Short tons	Value
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	v alue	Short tons	Y alue
izona			46, 560	\$63, 495					46, 560	<b>\$63,</b> 4
kansas	(2)	(2)	(2)	(2)	(2)	(2) \$41, 605	122, 840	\$61, 552	5, 656, 790	(2) 4, 274,
lifornia	1, 631, 430 (2)	\$2, 083, 923 (2)	3, 723, 610	2, 087, 543	178, 910 (2)	(2)	122, 040	ф01, 552	116,660	65,
orida	(-)	(9), (	[ 2]	2	(-)		(2)	(2)	69, 260	63,
nois			20, 930	ìź, 700	7				20, 930	15,
liana			(2)	(2)		10 457	-		366, 510	(2) 51
nsas 8			261, 780 (2)	38, 517 (²)	104, 730	13, 457	-		7, 180	(2)
ineryland	1. 980	1, 823	5, 200	9, 260					7, 180	`íı
rylandsachusetts	24, 870	30, 700	81, 300	101, 625					100,170	132
phigan	21,010		(2)	(2)			(2)	(2)	(2)	(2)
souri *			4 974, 660	4 261, 987	1, 510, 550	225, 618			4 2, 485, 210	4 48
vada			50, 820	72, 415			1,310	11, 781	50,820	72 1
w Hampshire			(2)	(2)	(2)	(2)		(2)	(2), 310	(2)
w Jersey w York	(2)	(2)		(2)	(2) (2)	(2) (2)	(2)	(2) (2)	239, 200	ìí
th Carolina	(-)	(-)	105, 970	133, 373					105, 970	133
0			(2)	(2)					(2)	(2)
ahoma *			1, 189, 100	167, 112	2, 394, 030	342, 663			3, 583, 130	50
gon			77, 330	47, 500			70, 470	442, 190	77, 330   171, 650	4° 56
msylvania	120	115	101, 060	126, 348			70, 470	442, 190	(2)	(2)
ode Island				(2) (2) 23, 597					(2)	(2)
th Carolinath Dakota	80	80	21, 830	23, 597					21, 910	`.2
nnessee	00	1		(2)					(2)	(2)
(88			(2)	$\binom{2}{2}$	(2)	(2)			227, 450	17
h							(2) (2) (2)	(2) (2) (2)	(2)	(2) (2)
mont				(2) (2)				\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\\	55, 860	15
rinia	(2) 12, 000	(2) 12,000	(2) (2) 32, 200	14, 235			(")	(*)	44, 200	2
shington	12,000	12,000	(2)	(2)					(2)	(2)
st Virginiasconsin			2	(2)	(2)	(2)			(2)	(2)
distributed	116, 830	128, 772	1, 131, 510	964, 440	(2) 675, <b>4</b> 30	(2) 447, 328	97, 460	227, 545	1, 312, 800	1, 19
MIN 10 10 10 10 10 10 10 10 10 10 10 10 10	1, 787, 310	2, 257, 413	7, 823, 860	4, 127, 147	4, 863, 650	1, 070, 671	292, 080	743, 068	14, 766, 900	8, 19
verage unit value	2, 131, 010	\$1.26	., 520, 500	\$0.53	2,230,000	\$0.22		\$2.54		•

<sup>1</sup> Includes stone used for filler (unspecified), poultry grit, refractory, road base, roofing granules, tennis courts, and terrazzo.

2 Included under "Undistributed."

3 Chats; figures collected by Joplin (Mo.) office of the Bureau of Mines.

#### MARKETS

As crushed stone is an important building material, sales generally are related closely to the volume of building construction. One of its leading uses is as aggregate in concrete, therefore sales should normally follow the trends of cement shipments and the area of concrete pavements that are constructed. These relationships are indicated in figure 3. Concrete aggregate failed to pace the enormous increase in total building because concrete was employed less extensively in the temporary or semipermanent types of structures erected in 1942 than in normal peacetime structures.




FIGURE 3.—Crushed-stone aggregates (concrete and road metal) sold or used in the United States compared with shipments of portland cement, total construction (value), and concrete pavements (contract awards, thousands of square yards), 1932–42. Data on construction and concrete pavements from Bureau of Foreign and Domestic Commerce.

Pig-iron production, which reached more than 59 million tons in 1942, surpassed all previous records, and therefore the demands for limestone furnace flux were unprecedented. To produce more than 86 million tons of steel, mills were forced to capacity. To replace burned-out furnace linings and to keep them in repair placed an unusual burden on producers of dolomite for refractory use and of ganister for manufacture of silica brick. The relations of fluxingstone output to pig-iron production and of refractory stone to steelingot manufacture over an 11-year period are indicated in figure 4. The demand for refractory stone in excess of normal requirements of the iron and steel industries, as indicated in this figure, probably was due to the shorter life of furnace linings under the stress of forced output.




FIGURE 4.—Sales (tons) of fluxing stone and refractory stone including that used in making lime as recorded in the chapter on Lime compared with production of steel ingot and pig iron, 1932-42. Statistics of steel-ingot production compiled by American Iron and Steel Institute.

#### NEW DEVELOPMENTS

Little is to be reported for 1943 on new plant construction or plant rehabilitation because necessity had to be shown and priorities obtained for all new equipment. Some increased facilities were authorized where the quarry output was used in military projects. Quarry operators had difficulty at times in obtaining necessary supplies and repairs, and their ingenuity and inventiveness were exercised in devising ways and means of coping with equipment difficulties. Used equipment was accommodated to replacement needs in some instances.

A good example of ways in which valuable materials are conserved is a method devised for reusing drill steel that ordinarily would be unserviceable. High-carbon drill steel is in heavy demand, and to maintain maximum supplies short lengths and broken quarry drills are now reclaimed by joining them into long drills. This is accomplished by skillful oxyacetylene welding.

## FOREIGN TRADE

Exports and imports of stone are relatively small. Figures for a recent 5-year period are shown in the accompanying table. Average exports for the 3-year period, 1938 to 1940, for which figures are comparable, were only 0.1 percent of average domestic sales during the same period. Average imports for the 4 years, 1937 to 1940,

were only 0.5 percent of average domestic sales for that period. Owing to wartime restrictions, no figures on foreign trade can be published, but it is apparent from the data on foreign movement of stone recorded herein that their absence for 1942 will not detract appreciably from the value of the report, particularly in view of the recent rigid restrictions on foreign movement of commodities deemed unessential to the war program. Foreign trade figures will be released at the termination of the present war emergency to preserve the continuity of the statistical record.

Value of United States exports and imports of stone, 1937-41

	Exports			Imp	orts		
Year	Marble and other building and mon- umental stone	Marble	Granite	Quartzite	Travertine	Other	Total
1937	1 \$88, 528 141, 815 134, 416 158, 008 108, 706	\$435, 361 301, 671 335, 696 209, 675 100, 859	\$245, 819 249, 573 165, 167 29, 760 14, 786	\$249, 003 224, 738 199, 454 190, 599 111, 055	\$18, 677 32, 313 29, 211 23, 468 3, 295	\$32, 566 30, 223 83, 197 70, 336 35, 527	\$981, 426 838, 518 812, 725 523, 838 265, 522

Marble only.
 January to September, inclusive.

Exports.—Marble is the principal variety of stone exported. Normally over 90 percent of the exports are shipped to Canada and the remainder chiefly to Cuba, Newfoundland, Mexico, and various Central and South American countries. Before the war small quantities were shipped to Germany, the United Kingdom, and other parts of Europe.

Imports.—Before the war Italy, France, Belgium, and Spain were the chief sources of foreign marbles. Mexico and Argentina are the principal suppliers of onyx marbles.

Moderate quantities of granite are imported from Canada, and when shipping was unrestricted Finland and Sweden were the most important sources outside of the American continent. Red granite from Finland is popular for polished monumental work, and gabbro (black granite) from Sweden finds a ready market, particularly in the New York area. Other European countries have furnished limited

Quartzite imports originate in Canada and are used principally for the manufacture of ferrosilicon. Travertine has been obtained almost exclusively from Italy. Before 1940 it was an important foreign building material that was popular thoughout the United States for floor tile, steps, and wainscoting.

## SLATE

## By OLIVER BOWLES AND M. S. JENSEN

#### SUMMARY OUTLINE

	Page	per - 1965년 - 경기는 경기를 보고 있었다.	Page
Summary	1255	Prices	1259
Salient statistics	1256	Price history	1259
Sales	1257	Review by States and districts	1260
Dimension slate		New developments	1262
Granules and flour	1258	Foreign trade	1263

## SUMMARY

Sales of slate as dimension stone were 41 percent lower in quantity and 33 percent lower in value in 1942 than in 1941. This drastic decline may be attributed chiefly to rigid curtailment of private residential building and small demand for slate in the types of defense-housing units that were constructed in 1942. Very few homes of the type that commonly have slate roofs were erected during the year. Unit prices were in general higher than in 1941.

Roofing-slate sales were little more than half as great as in 1941, in quantity or value; the average value per square in 1942 was \$8.87, whereas in 1941 it was \$8.39. Sales in the Pennsylvania area were 49 percent lower, in both quantity and value, than in 1941. In the New York-Vermont area, sales declined 49 percent in quantity and 39 percent in value. Virginia sales dropped 49 percent in quantity and

48 percent in value.

Sales of mill stock declined only about 1 percent in quantity but gained 3 percent in value. Sales of electrical slate, which made phenomenal gains in 1941, made a further advance of 10 percent in quantity and 14 percent in value in 1942, attaining the highest level of production since 1930. These gains during the past 2 years undoubtedly reflect the great increase in utilization of electric power in connection with the enormous growth in manufacture of war munitions. Although total new construction increased from 208 percent of the 1935–39 average in 1941 to 261 percent in 1942, sales of structural and sanitary slate declined 1 percent in quantity; they gained 3 percent in value. It is evident that the types of military building that predominated in the construction field in 1942 require less slate than peace-time building. Sales of vaults and covers increased 2 percent in quantity and value.

A decline of only 6 percent in quantity and 10 percent in value of blackboards and bulletin boards, even though school and college construction was almost negligible, indicates that blackboards found considerable use in military instruction centers. A decline of 31 percent, in both quantity and value, in sales of billiard-table tops indicates that they are not essential from a military standpoint. Sales of

A CONTRACTOR OF THE PROPERTY O

school slates increased 8 percent in quantity and 15 percent in value. Sales of flagstones and stepping stones were lower than in 1941.

Statistics on slate granules and flour are included in this chapter, although these products have little connection with the dimensionslate industry, except that granules are used in roofing products that compete in the roofing-slate market. For the most part, slate used for the manufacture of granules is unsuitable for other slate products. Sales of granules increased 10 percent in quantity and 9 percent in value and sales of flour 12 percent in quantity and 13 percent in value compared with 1941. Granules are used chiefly in the manufacture of low-cost roofing, and their wide employment was to satisfy the demands of military camps, warehouses, and other more or less temporary structures built for military needs. In 1942, the average sales value of granules f. o. b. mill was \$8.29 and of flour \$3.53 per short ton, compared with \$8.37 and \$3.49, respectively, in 1941. Figures for sales of granules made of rock other than slate are given in the chapter of this volume on Stone.

The following table, presenting the principal statistical data for the slate industry during 1941 and 1942, is arranged to permit ready

comparison of the 2 years.

Salient statistics of the slate industry in the United States, 1941-42

		1941				1942	1 150 L		
	Quar	Quantity		Quai	ntity .		Percent of change in—		
	Unit of measure- ment	Approximate equivalent short tons	value	Unit of measure- ment	Approximate equivalent short tons	value	Quantity (unit as reported)	Value	
Domestic production (sales by producers): Roofing slate	Squares 378, 980	140, 830	\$3, 180, 766	Squares 192, 070	71, 400	\$1, 704, 053	-49.3	-46.	
Mill stock: Electrical slate Structural and sanitary	Sq. ft. 628, 720	5, 870	477, 047	Sq. ft. 692, 680	6, 640	543, 531	+10.2	+13.	
SlateGrave vaults and cov-	738, 220	5, 740	254, 616	727, 490	5, 880	263, 390	-1.5	+3.	
ers Blackboards and bulle-	255, 890	2, 410	63, 030	260, 230	2, 510	64, 250	+1.7	+1.	
tin boards Billiard-table tops School slates	857, 990 241, 620 1 522, 830	2, 230 1, 880 550	198, 466 71, 388 12, 267	804, 860 166, 250 1 561, 900	1, 980 1, 210 500	178, 002 49, 205 14, 048	-6.2 -31.2 +7.5	-10. -31. +14.	
Total mill stock Flagstones, etc.2	3, 245, 270 3, 002, 380	18, 680 21, 480	1, 076, 814 152, 254		18, 720 16, 910	1, 112, 426 139, 328	-1. 0 -16. 7	+3. -8.	
Total slate as dimension stone Granules and flour		180, 990 437, 670	4, 409, 834 3, 105, 800		107, 030 483, 740	2, 955, 807 3, 404, 416	-40.9 +10.5	-33. +9.	
Grand total domestic pro- duction		618, 660	7, 515, 634		590, 770	6, 360, 223	-4.5	-15.	

Square feet approximate. Number of pieces: 1941, 977,250; 1942, 1,050,270.
 Includes walkways, stepping stones, and miscellaneous slate.

#### SALES

Dimension slate.—All slate products except granules and flour are classed as dimension slate because they consist of blocks or slabs cut to specified sizes and shapes. The following table shows sales of such products for a 5-year period.

Slate (other than granules and flour) sold by producers in the United States, 1938-42

	5.	Roofing		Mill	stock	Oth	er 1	Total		
Year	Squares	Approximate equivalent short tons	Value	Approximate short tons	Value	Approximate short tons	Value	Approximate short tons	Value	
1938	322, 040 399, 320 347, 130 378, 980 192, 070	149, 410 127, 600	\$2,247,910 2,868,961 2,436,123 3,180,766 1,704,053	16, 310 21, 710 17, 070 18, 680 18, 720	\$853, 602 1, 168, 671 935, 810 1, 076, 814 1, 112, 426	7, 790 8, 480 9, 780 21, 480 16, 910	\$63, 839 63, 493 64, 435 152, 254 139, 328	143, 690 179, 600 154, 450 180, 990 107, 030	\$3, 165, 351 4, 101, 125 3, 436, 368 4, 409, 834 2, 955, 807	

<sup>&</sup>lt;sup>1</sup> Includes flagstones, walkways, stepping stones, and miscellaneous slate.




FIGURE 1.—Sales of roofing slate and mill stock compared with new dwelling units and total new construction, 1920–42. Data on new construction from Bureau of Foreign and Domestic Commerce and on new dwelling units from Bureau of Labor Statistics.

Figure 1 compares sales of roofing slate and mill stock with the number of new dwelling units and total new construction from 1920 to 1942. Roofing slate, which is used chiefly in residential construction, failed to keep pace with new dwelling units from 1921 to 1929. From that date until 1938, residential building was at a low ebb, with roofing-slate sales showing small proportional gains. From 1939 to 1941, new residential building made rapid strides and slate roofing made relatively small gains. In 1942, residential construction underwent a decline comparable in severity with that of 1929; and roofing-slate sales, already at a low level, experienced a similar decline.

Mill stock is used most widely in nonresidential building. As indicated in figure 1, mill-stock sales maintained a favorable position with respect to total new construction from 1920 to 1937, but thereafter

they lagged. The demand for mill stock failed to respond to the upsurge of total construction in 1941 and 1942 because the predominant military construction consisted largely of temporary structures, in

which little or no slate was used.

Figure 2 presents graphically a statistical history of slate by uses over a 28-year period. All branches of the industry experienced a serious decline during the depression years, and although some recovery took place in subsequent years the upturn was reversed in 1942 because dimension slate is used very little in military building. Slate-granule sales, however, have expanded, because slate-surfaced composition roofing is in wide demand for temporary and semipermanent building.




FIGURE 2.—Value of slate sold in the United States, 1915-42, by uses.

Figure 3 presents the same history as figure 2, except that quantities rather than values are used. Products of low unit value naturally assume greater prominence in this chart, whereas the higher-priced products, such as blackboards, become relatively insignificant on a quantity basis.

Granules and flour.—Slate granules are used extensively in surfacing prepared roofing; and slate flour is employed as a filler in paints, road asphalt-surface mixtures, roofing mastic, oilcloth, linoleum, and various other products. The use of these commodities showed substantial gains in 1942 because of their application to military needs.

以及教皇不敢所述 不敢不敢職門在下京於

Crushed slate (granules and flour) sold by producers in the United States. 1938-42

• • • • • • • • • • • • • • • • • • •	Gran	nules	Flo	ır	Total		
Year	Short tons	Value	Short tons	Value	Short tons	Value	
1938	258, 930 265, 830 230, 440 323, 740 356, 510	\$2, 220, 306 2, 312, 177 2, 009, 151 2, 708, 246 2, 955, 562	90, 070 85, 950 88, 560 113, 930 127, 230	\$269, 656 268, 912 292, 750 397, 554 448, 854	349, 000 351, 780 319, 000 437, 670 483, 740	\$2, 489, 962 2, 581, 089 2, 301, 901 3, 105, 800 3, 404, 416	




FIGURE 3.—Quantity of slate sold in the United States, 1915-42, by uses.

#### **PRICES**

The average price of roofing slate f. o. b. quarry or mill, as reported to the Bureau of Mines, increased 48 cents a square in 1942 compared with 1941. In Pennsylvania it increased 14 cents, in the New York-Vermont area \$1.57, and in Virginia 23 cents a square.

The price of mill stock increased from 33 cents a square foot in 1941 to 35 cents in 1942. Average values of electrical and structural and sanitary slate increased 2 cents a square foot; those for vaults and covers and billiard-table tops remained unchanged; those for blackboards and bulletin boards decreased 1 cent a square foot; and those

for granules and flour decreased 6 cents a short ton.

Price history.—Figure 4 shows the trend in slate prices compared with building materials in general over a 28-year period. Slate prices were lower than those of building materials in general from 1915 to 1920, but from that time until 1932 prices of both roofing and mill stock were well above the average of all building materials. Since 1932 slate prices have varied only moderately from the general average.




FIGURE 4.—Prices of slate compared with wholesale prices of building materials in general, 1915-42.

Wholesale prices are from Bureau of Labor Statistics.

# REVIEW BY STATES AND DISTRICTS

The following table gives sales of slate in 1942, by States and uses.

Slate sold by producers in the United States in 1942, by States and uses

		Ro	ofing	Mill	stock		
State	Opera- tors	Squares (100 square feet)	Value	Square feet	Value	Other uses <sup>1</sup> (value)	Total value
Arkansas California Georgia Maine Maryland New York Pennsylvania 3 Vermont Virginia Undistributed	2 1 1 2 1 8 22 26 5	1, 130 2, 200 125, 950 41, 850 20, 940	\$9, 100 32, 518 1, 068, 300 396, 601 197, 534	604, 200 2, 530, 900 78, 310	\$471, 291 	(2) (2) (2) (2) (2) (2) (3) (4) (2) (2) (3) (4) (4) (5) (6) (6) (6) (7) (7) (7) (7) (7) (7) (7) (7) (7) (7	(2) (2) (2) (3) \$480, 391 (2) 659, 590 2, 606, 799 1, 659, 789 (2) 953, 654
Total: 1942 1941			1, 704. 053 3, 180, 766	3, 213, 410 43, 245, 270	1, 112, 426 41, 076, 814	3, 543, 744 43, 258, 054	6, 360, 223 7, 515, 634

Flagging and similar products, granules, and flour
 Included under "Undistributed."
 For details of production in Pennslyvania, see following table,
 Small amount of mill stock from New York in 1941 included under "Other uses."

SLATE 1261

Maine.—Slate produced in Maine is used chiefly for electrical panels, for which it possesses superior qualities. Sales of this product increased 16 percent in quantity and 14 percent in value compared with 1941. Sales of roofing slate were approximately only one-third as large in quantity and value as in 1941; such slate, however, is a small fraction of the Maine slate industry.

New York-Vermont.—Continuing the decline in roofing-slate sales recorded for the 2 preceding years, sales in 1942 were little more than half as great as in 1941; the value of sales declined 39 percent. Millstock sales declined 44 percent in quantity and 13 percent in value; but the value of other products, chiefly granules and flour, dropped less than 1 percent. The value of all slate products sold in Vermont in 1942 was 14 percent and in New York 4 percent lower than in 1941. This slate area is the outstanding source of colored roofing slates in the United States. Their attractive green, red, purple, and mottled colors and adaptability to architectural design, combined with excellent enduring qualities, fit them especially for churches, libraries, colleges, and Government and other public buildings, as well as for moderate- and high-priced homes. It was because such types of construction were so lacking in 1942 that the roofing-slate industry of the New York-Vermont area declined so severely.

Peach Bottom district.—Blue-black slates of high quality have been quarried for more than 200 years on the Maryland-Pennsylvania border near Delta, Pa. Many years ago several companies produced roofing slate in this area, but all ceased operation because of drainage difficulties and costly slides of overburden and debris. In 1937 a new roofing-slate operation was developed in Pennsylvania, and it has become a substantial producer. Granules and slate flour are

manufactured in both States.

Lehigh district.—The most productive slate area in the United States is in Lehigh and Northampton Counties, Pa.; all kinds of slate products are manufactured. As separate figures cannot be shown for York County, Pa., it is included with Northampton County in the

accompanying table.

The value of total sales of slate products in the Lehigh district was 25 percent lower in 1942 than in 1941. Sales of roofing slate were 49 percent less in both quantity and value. The following mill-stock products gained in both quantity and value: Structural and sanitary slate (8 percent in quantity and 18 percent in value), vaults and covers (2 percent in both quantity and value), and school slates (7 percent in quantity and 15 percent in value); the following declined in both quantity and value: Electrical slate (26 percent in quantity and 28 percent in value), blackboards and bulletin boards (6 percent in quantity and 10 percent in value), and billiard-table tops (30 percent in quantity and 29 percent in value). Other products, chiefly granules and flour, gained 20 percent in value compared with 1941.

Slate sold by producers in Pennsylvania in 1942, by counties and uses

교육 1 - 1 1 교육 1 2 4 21 - 1 일 : 1 중 2 2 2 3 3 3 3 3 3			Roofi	ng sla	ite			4-1			Mill	sto	k			W. 123	
County	Oper- ators		Squares (100	100			Elec	trica	1	Structural a							
Lehigh			square feet)	Va	Value		Square feet				ue Square feet		V	alue	Square feet		Value
		6 10, 510 16 115, 440											\$2, 098 41, 910		(¹) 251, 380	(¹) ¹ \$61, 057	
Total: 1942			125, 950 248, 980	1, 068 2, 075	, 300 , 490	58, 79,	880 260	25, 35,	523 496	687, 638,			, 008 , 881		380 700	61, 057 59, 659	
				М	ill sto	ck-	Con	tinu	ed						1		
County			kboards bulletin boards		Bi	lliar to	d-tal ps	ole	s	chool	slate	es	us	her ses lue)		Fotal value	
		Squa		alue	Squ fee	are et	Va	lue		uare et	Va	lue			. 4.3 2.8.		
Lehigh Northampton and York	2	246, 8 558, 3		, 311 , 691	166,	250	\$49,	205	561	900	\$14,	048	³ \$966	³) 5, <b>6</b> 56	13	\$152, 787 , 454, 012	
Total: 1942 1941		804, 8 857, 9		, 002 , 466	166, 238,	250 850		205 674		900 830	14, 12,			, 656 , 415		, 606, 799 , 464, 348	

<sup>1</sup> Small amount of slate for grave vaults and covers produced in Lehigh County included under Northamp-

ton and York Counties.

2 York County produced roofing slate, granules, and flour only.

3 Small amount of flagging produced in Lehigh County included under Northampton and York Counties.

## NEW DEVELOPMENTS

The possibilities of using waste slate as a source of lightweight aggregates have been studied by the Bureau of Mines, and the results appear in a recent publication. Slates from Pennsylvania, Maine, and Maryland gave a satisfactory degree of bloating upon calcination. Concretes made with the resulting aggregates weighed 103 to 107 pounds per cubic foot, whereas concretes made with standard crushed-stone or gravel aggregates weigh about 142 pounds per Concrete made with expanded slate aggregates was found to possess adequate strength for general structural uses. lightweight concretes can be used advantageously for bridge decks, arches, floors, and walls where the structural design demands a minimum dead load. As enormous quantities of waste accumulate in all slate-producing centers, the development of such a byproduct industry is highly desirable.

The results of a survey of roofing materials in the South Central States, recently published by the National Bureau of Standards,<sup>2</sup> bring out the interesting fact that slate covered only 0.75 percent of all the roofs examined. In view of the fact that one of the major roofing slate-producing regions of the United States-Buckingham

<sup>1</sup> Conley, John E., Waste Slate as a Raw-Material Source of Lightweight Aggregates: Trans. Am. Inst. Min. and Met. Eng., vol. 148, Industrial Minerals (Nonmetallics), 1942, pp. 161-166.

2 Snoke, Hubert R., and Waldron, Leo J., Survey of Roofing Materials and Structures: U. S. Dept. of Commerce Building Materials and Structures Report, BMS 84, 1942, 19 pp.

1263 SLATE

County, Va.—is within easy reach of the northern part of the area covered in the survey, it is remarkable that slate, which possesses superior durability and attractive appearance, should have been used The potential market for roofing slate is enormous, so sparingly. but the industry has made little progress in developing the market.

Considerable publicity has been given to a patent process of laying roofing slate with a single lap over heavily coated asphalt roofing. Each slate is held in place with a single nail and a metal clip. advantages claimed are a reduction of nearly 50 percent in the quantity of slate needed, weight of roof, and cost, compared with roofs laid according to the American method. At the same time, the roof is said to equal the ordinary slate roof in appearance and durability. Wide acceptance of this new method by architects and builders would tend greatly to increase the use of roofing slate, particularly in the field of low-cost housing where slate is commonly regarded as too costly for extensive use.


## FOREIGN TRADE

Owing to wartime restrictions no figures on foreign trade can be published; they are, however, of so little significance in the slate industry that their absence will not detract appreciably from the value of this report.

The total annual value of imports for the 10-year period 1932 to 1941 ranged from a high of \$17,317 in 1932 to a low of \$520 in 1940 and averaged about \$7,000 a year. This is only about 0.2 percent of the average annual domestic sales for the period. These small imports originated in various countries, chiefly Italy, Poland, Nether-

lands, Czechoslovakia, and United Kingdom.

Exports of slate products (exclusive of granules and flour), as reported by producers, are higher than imports. From 1932 to 1941 their value ranged from \$26,042 in 1933 to \$75,656 in 1940 and averaged about \$55,000 a year. This is a little more than 1 percent of the average annual sales value (including granules and flour) during the Exports consist of roofing, school slates, electrical slates, blackboards, billiard-table tops, and various structural slate products. Canada, Mexico, and South and Central America are the principal destinations.



## SAND AND GRAVEL

By G. W. Josephson and G. E. Tucker

#### SUMMARY OUTLINE

	Page		Page
Summary	1265	Principal trends	1275
Salient statistics	1266	Sand and gravel for construction	
Production	1267	Industrial sands	
Government-and-contractor production	1273	Employment and productivity	
Method of transportation	1274	Prices New developments	1279
Degree of preparation	1274	Foreign trade	1279
Size of plants		Blast-furnace slag	1280

## SUMMARY

As an integral part of the great wave of wartime construction, the production of sand and gravel in 1942 exceeded 300 million tons and surpassed all previous records. The quantity and value of total production over a period of years are indicated in figure 1.




FIGURE 1.—Total production of sand and gravel in the United States, 1905-42.

With the increase in activity came an appreciable improvement in production efficiency and firmer prices, counterbalanced by rising operating expenses in the form of increased wage, transportation, and material costs. The War Production Board, the Office of Price Administration, and the Office of Defense Transportation greatly influenced the practices of the industry in 1942.

A noteworthy trend is visible in the fact that whereas commercial operations increased their tonnage 28 percent in 1942 compared with 1941, the output of Government-and-contractor 1 operations was 33

<sup>&</sup>lt;sup>1</sup> Prior to 1939 classified as "noncommercial"; details of change in designation given in Minerals Yearbook, 1940, Review of 1939, p. 1214.

percent lower. Private building, highway construction, and many large public works projects like those of the Work Projects Administration have been curtailed or eliminated to concentrate the men, money, equipment, and materials on more critical wartime activities. Salient statistics on sand and gravel for 1941 and 1942 are summarized in the following table.

Sand and gravel sold or used by producers in the United States, 1941-42, by commercial and Government-and-contractor operations and by uses

		1941			1942		Parac	nt of
		Valu	в		Value	e	chang	
	Short tons	Total	Aver-	Short tons	Total	Aver- age	Ton- nage	Aver- age value
COMMERCIAL OPERATIONS								
Sand: Glass. Molding. Building. Paving. Grinding and polishing <sup>1</sup> Fire or furnace. Engine. Filter. Railroad ballast <sup>2</sup> Other <sup>3</sup> Total commercial sand.	7, 246, 081 40, 164, 731 27, 013, 283 1, 001, 814 325, 803 2, 022, 782 263, 966 1, 634, 335 2, 022, 604	8, 412, 725 21, 698, 378 14, 834, 378 1, 388, 966 357, 240 1, 312, 433 324, 107 445, 181 1, 455, 384	1. 16 . 54 . 55 1. 39 1. 10 . 65 1. 23 . 27	8, 255, 991 46, 035, 701 33, 307, 106 806, 878 368, 465 2, 559, 008 176, 833 1, 969, 758 1, 698, 134	10, 745, 552 26, 901, 356 20, 035, 796 1, 363, 168 491, 972 1, 749, 204 223, 137 675, 778 1, 345, 823	1. 30 . 58 . 60 1. 69 1. 34 . 68 1. 26 . 34 . 79	-19.5 +13.1 +26.5 -33.0 +20.5	+12. +7. +9. +21. +21. +2. +25. +9.
Gravel: Building Paving Railroad ballast 4 Other 4	37, 900, 243	26, 729, 788 24, 624, 898 5, 456, 300	.71 .64 .33	46, 389, 536	35, 827, 822 43, 193, 937 8, 377, 991	.77 .71 .36	+ 22. 4 +58. 9	+8. +10. +9.
Total commercial gravel_	96, 385, 957	58, 364, 592	. 61	134, 147, 426			+39. 2	+8.
Total commercial sand and gravel	181, 556, 467	114, 706, 913	. 63	232, 947, 787	159, 427, 273	. 68	+28.3	+7.
GOVERNMENT-AND-CONTRACTOR OPERATIONS 6								
Sand: Building Paving	5, 789, 000 12, 876, 000	1, 797, 000 4, 013, 000	. 31 . 31	3, 482, 000 5, 089, 000	2, 018, 000 2, 109, 000	. 58 . 41	-39.9 -60.5	
Total Government-and- contractor sand	18, 665, 000	5, 810, 000	. 31	8, 571, 000	4, 127, 000	. 48	-54.1	+54.8
Gravel: Building Paving	8, 779, 000 79, 715, 000	3, 797, 000 22, 893, 000	. 43	8, 022, 000 54, 806, 000	3, 942, 000 21, 004, 000	. 49	-8.6 -31.2	+14.0 +31.0
Total Government-and- contractor gravel	88, 494, 000	26, 690, 000	30	62, 828, 000	24, 946, 000	. 40	-29.0	+33.
Total Government-and- contractor sand and gravel	107, 159, 000	32, 500, 000	30	71, 399, 000	29, 073, 000	. 41	-33.4	+36.
COMMERCIAL AND GOVERNMENT- AND-CONTRACTOR OPERATIONS								
Sand Gravel	103, 835, 000 184, 880, 000			107, 371, 000 196, 975, 000	74, 443, 000 114, 057, 000	. 69 . 58	+3.4 +6.5	+15.0 +26.1
Grand total	288, 715, 000	147, 207, 000	. 51	304, 346, 000	189, 500, 000	. 62	+5.4	

Includes blast sand as follows—1941: 371,049 tons valued at \$912,626; 1942: 422,922 tons, \$1,071,018.

Includes ballast sand produced by railroads for their own use as follows—1941: 37,911 tons valued at \$5,676; 1942, 39,862 tons, \$8,740.

Includes some sand used by railroads for fills and similar purposes as follows—1941: 351,537 tons valued at \$36,737; 1942: 178,191 tons, \$27,500.

Includes ballast gravel produced by railroads for their own use as follows—1941: 7,536,591 tons valued at \$1,506,121; 1942: 10,243,680 tons, \$2,031,339.

Includes some gravel used by railroads for fills and similar purposes as follows—1941: 1,157,557 tons valued at \$128,993; 1942: 1,294,861 tons, \$141,917.

Approximate figures for States, counties, municipalities, and other Government agencies directly or under lease.

## PRODUCTION

Approximately 5 percent more sand and gravel was produced in 1942 than in 1941 and for the fourth successive year a new record was attained. As stocks of sand and gravel held by producers are small in tonnage and not subject to great variation from year to year, the quantity of materials sold or used is virtually equivalent to production. Throughout this report, sales and production are used interchangeably. The following table summarizes total production of sand and gravel during the 5-year period 1938-42.

Sand and gravel sold or used by commercial and Government-and-contractor producers in the United States, 1938-42

Year	Sa	Sand Gravel (including rail- road ballast) Total					
- Py	Short tons	Value	Short tons	Value	Short tons	Value	
1938	57, 113, 828 72, 542, 000 78, 674, 000 103, 835, 000 107, 371, 000	\$33, 935, 725 41, 608, 000 45, 332, 000 62, 152, 000 74, 443, 000	124, 206, 405 153, 466, 000 159, 634, 000 184, 880, 000 196, 975, 000	\$51, 987, 122 64, 458, 000 65, 356, 000 85, 055, 000 114, 057, 000	181, 320, 233 226, 008, 000 238, 308, 000 288, 715, 000 304, 346, 000	\$85, 922, 847 106, 066, 000 110, 688, 000 147, 207, 000 188, 500, 000	

Details of production in 1942, by States and uses, are presented in the following tables. California, with the greatest tonnage ever recorded from a single State, was the leading producer, and Texas, Illinois, New York, Michigan, Ohio, and Indiana followed in the order named.

Sand and gravel sold or used by commercial and Government-and-contractor producers in the United States in 1942, by States

State	Short tons	Value	State	Short tons	Value
AlabamaAlaskaArizona	(1)	\$2, 538, 738 (1) 1, 193, 603	New Hampshire New Jersey	6.032.978	\$159, 058 5, 726, 860 1 146, 866
Arkansas California Colorado	5, 831, 867 34, 791, 974	3, 919, 212 22, 067, 004 3, 220, 706	New Mexico New York North Carolina North Dakota	2, 509, 684	11, 841, 245 2, 491, 820 343, 612
Connecticut Delaware Florida	2, 960, 477 169, 267 1 1, 834, 863	1, 610, 583 95, 298 1 1, 339, 361	Ohio Oklahoma Oregon	13, 753, 393 3, 109, 630 6, 660, 311	10, 570, 888 1, 946, 644 4, 497, 514
Georgia Idaho Illinois	17, 720, 343	1, 732, 528 1, 983, 054 11, 532, 848	Pennsylvania Puerto Rico Rhode Island South Carolina	(1) 572, 437	10, 700, 743 (1) 361, 881 355, 170
Indiana Iowa Kansas Kentucky	6, 700, 745 5, 201, 000	6, 609, 929 2, 190, 452 2, 773, 283 1, 743, 695	South Dakota Tennessee Texas	3, 577, 983 1 3, 550, 427	1, 443, 908 1 3, 086, 499 11, 639, 412
Louisiana Maine Maryland	4, 615, 418 2, 249, 254	3, 551, 750 800, 147 5, 547, 434	Utah Vermont Virginia	3, 874, 841 476, 331	2, 079, 302 173, 258 5, 460, 232
Massachusetts Michigan Minnesota	1 5, 179, 419 15, 542, 941	1 3, 105, 674 7, 362, 231 2, 602, 324	Washington West Virginia Wisconsin	8, 172, 550 3, 058, 878	4, 094, 900 3, 747, 351 3, 496, 621
Mississippi Missouri Montana	3, 257, 551 4, 490, 650	1, 766, 367 2, 931, 924 2, 986, 468	Wyoming Undistributed 2	3, 978, 673	1, 613, 407 3, 569, 000
Nebraska Nevada	6, 527, 665	3, 241, 622 1, 508, 471	•	304, 346, 000	188, 500, 000

<sup>1</sup> Output of Government-and-contractor operations included under "Undistributed." 2 Includes items covered by "1."

Sand and gravel sold or used by commercial and Government-and-contractor producers in the United States in 1942, by States and uses

[Commercial unless otherwise indicated]

				Sa	and			
						Buile	ding	
State	G	lass	Mo	olding	Com	mercial		nent-and- ractor
	Short tons	Value	Short tons	Value	Short tons	Value	Short	Value
Alabama			105, 371	\$79, 752	940, 074	\$424, 835	2, 776	\$2,05
Alaska Arizona					100 550	145 010	-	
Arkanese	(1)	(1)	(1)	(1)	160, 558 709, 607	145, 316	206 108	907 21
Arkansas California	157 773	\$600, 190	155, 441	361, 900	5, 249, 990	460, 977 3, 088, 987	306, 185 1, 434, 788	297, 31 757, 79
Colorado	101,110		5, 331	5, 057	458, 924	235, 677	186, 644	184, 20
Connecticut	1.300	7,800	(1)	(1)	873, 682	441, 653	3, 380	2,02
Delaware			4.903	2,094	32, 484	22, 334	0,000	1
FloridaGeorgia	3, 300	1,650			529, 949	335, 976 114, 252	(1)	(1) (1)
Georgia	17, 996	35, 991	2,034	3, 764	228, 057	114, 252	(1)	(1)
Idaho			1		14, 473	7.855	313	7
Illinois Indiana	(-)	(1)	1, 984, 605	2, 210, 003	2, 722, 051	1, 266, 968	20, 089	11, 89
Iowa			300, 877	190, 834	1, 362, 693	643, 817	27, 401	2, 51
Kansas			(1)	(1)	682, 292 1, 209, 417	315, 330 566, 882	95 15, 919	5, 59
Kentucky			9, 356	19,095	595, 505	458, 161	123, 385	55, 29
Kentucky Louisiana			(1)	(1)	861, 184	413, 288	61	5
					116, 435	50, 681	1	
Maryland	14, 100	21, 150			(1)	(1)		
			(1)	(1)	1, 591, 079	871, 036	(1)	(1)
Michigan	(1)	(1)	1, 334, 410	598, 370	1, 433, 509	650, 530	6, 481	1, 65
Minnesota	(1)	(1)	23, 026	29, 168	784, 291	283, 664	16, 146	6, 27
Mississippi Missouri	(1)	(1)	107, 174	111, 473	357, 324	177, 070	26, 655	1,82
Montana	(-)	(9)	107, 174	111,473	1,001,232 121,769	534, 321 103, 842	37, 044 1, 341	27, 47
Nebraska			(1)	(1)	1, 133, 172	467, 517	489	2, 11
Navada	(1)	(1)	(i)	(1)	14, 563	20, 156	6, 132	9, 14
New Hampshire			, ,		(1)	(1)	0, 102	0, 11
New Jersey	321, 690	434, 031	1, 606, 571	2, 672, 342	1, 808, 279	933, 286		
New Hampshire New Jersey New Mexico New York North Carolina					(1)	(1)	(1)	(1)
New York			529, 809	851, 575	4, 847, 665	2, 852, 823	76, 975	(1) 115, 74
North Dakota					1, 170, 139	472, 991	197, 760	46, 519
Ohio	(1)	(1)	983, 607	1 705 976	2 550 570	1 662 056	972	6
Oklahoma	(1) (1)	(1) (1)	4, 236	1, 785, 376 6, 778	2, 550, 572 408, 244	1, 663, 056 253, 126	1, 321 16, 983	36, 926
Ohio Oklahoma Oregon		1	2, 200	0,110	480, 730	371, 593	6, 340	36, 926
Pennsylvania Puerto Rico Rhode Island	(1)	(1)	499, 665	832, 840	480, 730 2, 244, 761	2, 060, 238	29,000	10,000
Puerto Rico			l				(1)	(1)
Rhode Island			(1)	(1)	59, 611	35, 474	3, 576	3, 149
					332, 128	129, 666	44, 286	17, 787
South Dakota	10.000				100, 512	37, 973	532	285
Гennessee Гexas	10, 380 (1)	15, 570	111, 080	204, 383	703, 800	604, 782	(1)	(1)
Utah	. 0	(1)	(1)	8	2, 176, 122 491, 959	1, 466, 842	73, 867	24, 415
Vermont				100	(1)	286, 409	1, 915	719
Virginia	(1)	(1)	35, 334	37, 434	1, 454, 595	1, 005, 499	3, 369	508
Washington		l	5, 828	18, 925	1, 099, 649	554, 391	15, 796	6, 283
Washington West Virginia Wisconsin	(1)	(1)	(1)	(1)	332, 466	323, 960	823	983
Wisconsin			99, 448	132, 030	1, 087, 673	467, 826	127, 162	42, 45
Wyoming					70, 836	43, 516	376	454
Undistributed 2	3, 095, 948	5, 668, 045	347, 885	592, 359	1, 431, 646	1, 236, 780	666,000	341,000
	3, 622, 487	6, 784, 427	8, 255, 991	10, 745, 552	46, 035, 701	26, 901, 356	2 400 000	0.010.000
	0, 044, 101	0, 102, 241	U, 400, 001	10, 120, 002	20,000,401	,∡u, yu1, 300	3, 482, 000	2,018,000

Sand and gravel sold or used by commercial and Government-and-contractor producers in the United States in 1942, by States and uses—Continued

			Sand	l—Continu	ied			
		Pav	ing				4.5	
State	Comr	nercial		nent-and- ractor		ling and shing 3	Fire or	furnace
	Short tops	Value	Short tons	Value	Short tons	Value	Short tons	Value
Alabama	476, 657	\$240, 630	178, 605	\$10, 134 (1)			(1)	(1)
Arizona	39, 460	33, 083	55, 322	47, 675	275	\$212		
Arkansas	598, 136	309, 422	11, 792	15, 668	(1)	(1)		
California	3, 868, 982	2, 159, 780	708, 515	466, 714	(1)	(1)		
Colorado	22, 232 168, 359	9, 767 94, 255	69, 341 410, 688	27, 393 31, 279	(1)	(1)		
Delaware	36, 232	24, 726	410, 000	31, 219	4, 103	5, 961	143	\$347
Florida	600, 805	396, 173	(1)	(1)	1,100	0, 501	140	φυτ.
Georgia	546, 243	383, 406	(1)	(1)	9, 447	24, 747		
Idaho	(1)	(1)	144, 808	76, 657				-==-==
Illinois Indiana	1, 979, 556 1, 638, 374	1,041,040 907,244	5, 285	1, 924 8, 247	(1)	(1)	66, 837	77, 655
Iowa	362,077	173, 335	15, 401 21, 600	1,600	(1)	(1)	103, 920	52, 068
Kansas	1, 742, 606	899, 824	46, 371	20, 384	[6]	(1)		
Kentucky	215, 489	176, 209	2,744	1, 132				
Louisiana		301, 708	92	68	(1)	(1)		
Maine	62, 526	33, 300	146, 166	37, 292	650	250		
Maryland	407, 967	211, 655	22, 803	1, 689	(1)	(1)	(1)	(1)
Michigan	2, 141, 808	1, 113, 516	316, 322	66, 186	(1)	(1)		
Minnesota	396, 525	107, 737	221, 083	37, 582	234	585	220	220
Mississippi	439, 316	204, 647	12,040	524				
Missouri	527, 168	244, 197	3, 623	1,839	(1)	(1)		
Montana Nebraska		98, 260 1, 047, 352	935 24, 972	716 6, 277				
Nevada	56, 576	57, 014	5, 250	3, 173	146	402		
New Hampshire	26, 665	12, 624	308, 036	18, 152	110	102		
New Jersey	695, 419	351, 489	815	240	110, 203	233, 294	42, 659	57, 756
New Mexico			(1)	(1)				
New York	1, 867, 851	1, 112, 547	407, 064	480, 464	340	136	(1)	(1)
North Carolina North Dakota	667, 672 30, 943	224, 255 17, 764	664, 761 8, 969	130, 890 3, 102				
Ohio		1, 148, 097	22, 675	6,741	(1)	(1)	(1)	(1)
Oklahoma	338, 611	145, 422	86, 245	63, 189	4,000	2,000		
Oregon	382, 052	374, 170	25, 833	5, 833				
Pennsylvania	2, 181, 606	1,834,746	185	157	(1)	(1)	51, 118	86, 815
Ruerto Rico	00 107	17 107	(1)	(1) 10, 764				
South Carolina	28, 187	17, 197 37, 356	25, 468 37, 065	32, 411	1, 511	3, 372 (1)		
South Dakota	8, 633	4, 706	109, 410	43, 400	(-)	(-)		
Tennessee	739, 358	706, 468	(Í)	(1)	(1)	(1) (1)	486	570
Texas	1, 983, 210	1, 341, 602	143, 896	73, 778	(1)	(1)		
Utah	5, 778	3, 310	2,025	1, 142				<b>-</b>
VermontVirginia	11, 129 773, 013	6, 472 543, 369	3, 601 36, 766	1, 775 16, 300	(1)	(1)		
Washington	358, 171	227, 879	218, 864	83, 873	(1)	(1)		
West Virginia	290, 705	264, 928	13, 652	12, 873	(1)	(1)		
Wisconsin	275, 795	165, 002	250, 405	62, 964	34, 496	67, 346		
Wyoming		18, 800	10, 364	6, 977				
Undistributed 2	1, 632, 375	1, 209, 313	289,000	190,000	641, 473	1, 024, 863	103, 082	216, 541
	33, 307, 106	20, 035, 796	5, 089, 000	2, 109, 000	806, 878	1, 363, 168	368, 465	491, 972
	00, 007, 100	20, 055, 196	0, 089, 000	2, 109, 000	000, 8/8	1, 303, 108	308, 405	491, 8

Sand and gravel sold or used by commercial and Government-and-contractor producers in the United States in 1942, by States and uses—Continued

				Sand-0	Continued			
State	En	gine	Fi	lter	Railroad	ballast 4	Oth	er s
	Short tons	Value	Short	Value	Short tons	Value	Short tons	Value
Alabama	175, 655	\$39,968						
Alaska								
Arizona	21, 995	20, 567			5, 269	\$4,635	1, 260	\$1,60
Arkansas	(1)	(1)	(1)	(1)	(1)	(1)	8, 460	8, 47
California	(1)	(1)	4, 283	\$22,025	(1)	(1)	105, 718	93, 08
Colorado		37, 311					38, 333	21, 81
Connecticut			13, 681	7,080			14, 975	7, 12
Delaware	62, 655	21, 930	743	165	995	1,658	4, 351	1, 93
Florida		160	2, 482 3, 222	1, 241	4, 900	970	(1)	(1)
leorgia	12, 790	6,010	3, 222	12, 889			58, 711	37, 75
daho			(1)	(1)			17, 107	7,03
Hinois	140, 298 97, 644	80, 521 39, 706	(-)	(0)	(1) 138, 848	(1) 44, 787	126, 414	146, 96
ndiana		35, 431		(1)		(1)	31, 954 35, 723	13, 11 14, 81
owa Cansas		22, 582	(1)	(1)	(1)	(1)	36, 088	22, 21
Kansas		(1)		( )	(1)	(1)	(1)	(1)
Louisiana		6, 335			101, 895	55, 523	2,704	81
Maine	10,000	0,000			101,000	00, 020	3, 334	1, 33
Maryland	(1) -	(1)	(1)	(1)			(1)	(1)
Massachusetts	49, 299	(1) 23, 575	(1)	(1)			58, 180	17, 14
Michigan	(1)	(1)	400	200	227, 855	44, 056	72, 386	33, 55
Minnesota		(1)	(1)	(1)	206, 233	43, 209	39, 612	14.54
Mississippi	9, 052	3,046	l			10, 200	4, 109	1, 91
Missouri	40, 715	32,091	(1)	(1)	(1)	(1)	77, 198	111, 13
Montana		1,300	(1) (1)	(1)	(1)	(1)	23, 935	3, 24
Vebraska	(1)	(1)	l		(1)	(1)	17, 798	3, 70
Vevada							26, 270	23, 51
New Hampshire			2, 460 42, 082	4, 920		<b>-</b>		
New Jersey	47, 012	25, 256	42,082	55, 884	(1)	(1)	51, 778	48, 18
New Mexico	(1)	(1)						
New York	45, 850	35, 682	367	228	(1)	(1)	16, 492	8, 47
North Carolina	(1)	(1)			77, 875	22, 275	(1)	(1)
North Dakota			l:-:::-				(1)	(1)
)hio	90, 687	68, 997	6, 663	8, 938	31,000	9, 343	(1)	(1)
klahoma	64, 642	32, 679			500	300	(1)	(1)
regon	13, 992	2,694			22, 422	9, 796	24, 258	8, 50
Pennsylvania	392, 418	499, 056	(1)	(1)			131, 018	186, 79
Puerto Rico Rhode Island								
South Carolina	(1)	(1)	(1)	(1)	12,070	2, 473	(1)	(1)
South Dakota	(-)	(9)	(9)	(9)	7,000	1, 400	(-)	(0)
Cennessee	(1)	(1)	366	2, 562	7,000	1,400	1, 404	1, 42
Cexas	55, 225	20, 390	3, 559	15, 980	179, 366	102, 211	30, 554	10, 99
Jtah	(1)	(1)	0,000	10, 500	110,000	102, 211	(1)	(1)
Vermont	(1)	1 21					1, 525	58
Virginia	43, 260	21,755	51,660	20,664			56, 535	32, 76
Washington	(1)	(1)	(1)	(1)	20, 728	5,098	63, 428	24, 53
West Virginia	381, 885	356, 130					(1)	(1)
Wisconsin	(1)	(Í)	(1)	(1)	6, 427	1, 398	33, 999	16, 80
Wyoming	2, 100	1,470					4, 550	1,70
Jndistributed 2	664, 073	314, 562	44, 865	70, 361	926, 375	326, 646	477, 973	418, 20
	2, 559, 008	1, 749, 204	176, 833	223, 137	1, 969, 758	675, 778	1, 698, 134	1, 345, 82

Sand and gravel sold or used by commercial and Government-and-contractor producers in the United States in 1942, by States and uses—Continued

				Gr	avel			
	* 1	Build	ling			Pav	ing	
State	Comn	nercial		ent-and- actor	Comn	nercial	Governm contr	ent-and- actor
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
Alabama	1, 367, 900	\$995, 666	676	\$434- (1)	702, 178	<b>\$540,</b> 699	438, 232	\$25, 83
Maska	201, 160	206, 109	1,559	175	85, 054	71, 287	1, 020, 676	(1) 654, 48
Arizona Arkansas	1, 091, 304	206, 109 1, 052, 887 4, 989, 508	440, 758	433, 851	85, 054 699, 943 6, 562, 239	71, 287 446, 777	1, 216, 565	311, 78
alifornia	l <i>6</i> . 525. <b>4</b> 591	4, 989, 508	3, 725, 767	1, 678, 241	6, 562, 239	4, 594, 510	5, 192, 752	2, 827, 29
Colorado Connecticut	749, 864	517, 273 906, 754	366, 958	341, 409	486,664	476, 479 41, 744	2, 126, 045	1, 348, 88
Jonnecticut Delaware	1, 141, 738 7, 744	7, 450			71, 631 14, 914	6,700	102, 600	38,00
Clorida	557. 263	460, 649	(1)	(1)	72, 275	94, 269	(1)	(1)
Jaardia	21 848	21,848	(1)	(1) (1)	69, 586	91, 864	(1)	(1) (1)
daho llinois ndiana	(1)	(1)	14, 261	2,312 8,942	1, 126, 972	1, 274, 540	1, 050, 282 1, 137, 913 431, 179	448, 12
llinois	2, 395, 886 1, 227, 699 323, 631 364, 267	1, 186, 085	18, 140	8, 942 6, 508	2, 958, 191 4, 818, 854 1, 655, 503 950, 610	1, 692, 061 2, 498, 507 819, 745	1, 137, 913	834, 5
owa	323 631	833, 182 243, 462 231, 830	22, 484 75, 798	6,546	1 655 503	819 745	3 163 436	183, 42 381, 2
Zansas	364, 267	231, 830	10, 784	352	950, 610	579, 389	3, 163, 436 741, 744	366, 88
Kentucky	698, 981	500, 117	27,490	14, 803	279, 197 1, 174, 764	252, 758	190, 446	70.30
Kansas Kentucky Louisiana	1, 446, 137	1, 258, 946	164	55	1, 174, 764	1, 217, 779	72, 605	17, 30
Maine	65, 106	54, 151			737, 837	311, 154	955, 885	233, 38
Maryland Massachusetts		1, 143, 694	(1)	(1)	1, 292, 368	(1) 610, 531	286, 560	28, 37
Michigan	1 040 610	1, 206, 131	140, 907	20, 850	3, 927, 461	2, 144, 707	3, 141, 005	OŘÉ 6/
Minnesota	569, 743	496, 662	104, 989	31, 726	209 495	1/19 983	E 905 947	462, 8
Minnesota Mississippi Missouri	569, 743 707, 741 1, 128, 152 87, 806 598, 791	506, 903	144, 258	81, 916	772, 097 445, 867 2, 062, 433 1, 973, 104	547, 664 263, 035 1, 590, 722	370, 826 581, 161 1, 191, 837	462, 88 93, 26 317, 67 567, 25
Missouri	1, 128, 152	677, 162 77, 137	102	44, 759	445, 867	263, 035	581, 161	317, 67
Montana Nebraska	508 701	354, 086	81, 776 10, 353	1,885	1 973 104	1, 124, 584	325, 011	113, 9
Nevada	45, 519	45, 288	9, 160	15, 320	(1)	(1)	1, 424, 474	722, 1
New Hampshire	(1)	(1)			36, 739	38, 727	899,640	74, 8
New Jersey New Mexico	889, 675	656, 094			372, 477	224, 480	13, 963	1,0
New Mexico	0 251 041	(1)	(1) 204, 987	287, 109	0 604 206	1 007 079	0 000 040	(1)
New York	3, 351, 941 453, 003	2, 546, 872 527, 885	12, 735	287, 109 2, 419	2, 684, 326 896, 515	1, 897, 073 989, 894	2, 003, 942 70 126	1, 439, 33 32, 56
North Dakota	18, 184	17, 043	1.350	10	191 //12	107 /56	79, 126 1, 803, 314	65.9
OhioL	1, 979, 853	1, 349, 635	19, 361	10, 510	3, 380, 518	2, 289, 362	406, 594	87, 6
North Dakota Ohio Oklahoma	18, 184 1, 979, 853 207, 107 930, 233	120, 272	164	55	474, 799	389, 369	1, 316, 069 1, 492, 044	87, 68 643, 47 905, 79
Oregon Pennsylvania	930, 233 2, 143, 331	631, 965	116, 788	19, 837	3, 380, 518 474, 799 2, 672, 804 2, 075, 886	1, 902, 684 1, 847, 594	1,492,044	905,7
Pennsylvania Puerto Rico	2, 140, 551	2, 035, 193	(1)	(1)	2,010,000	1,011,094	112,658 (1)	23, 84 (1)
Rhode Island	53, 211	37, 631	4.519	3, 938	186, 975	75, 015	123, 681	25, 7
South Carolina	65, 415	64, 549	164	55	22, 037	21,044	545	2
South Dakota	100, 354	35, 408			1, 313, 211	958, 687	1, 501, 583	269, 54
rennessee rexas Utah	738, 063	610, 605 2, 798, 542	(1) 562, 498	(1) 74, 927	1, 075, 292 4, 107, 958	831, 755 3, 547, 745	3, 255, 012	(1) 1, 350, 2
ı uxus Utoh	3, 505, 326 664, 508	2, 798, 542 379, 266	5, 785	2,826	1, 308 266	926, 302	1 952 107	376, 66
Vermont	13, 570	17,000		l	38, 806	13 612	359, 974	122, 79
Virginia	13, 570 1, 754, 966	2, 265, 497	31, 350	8,742	1, 308, 266 38, 806 901, 719 1, 244, 989	1, 230, 329	359, 974 319, 734 2, 131, 388 194, 346	55, 8
Washington	1, 529, 689	893, 832	171,826	75, 030	1, 244, 989	1,003,672	2, 131, 388	796, 2
West Virginia	446, 486	422, 537	7,510	2,920	1 400.040	421, 995	194, 346	149,60
W ISCOUSIII Wroming	1, 288, 629 281, 595	640, 721 162, 947	490, 705 736		1, 468, 354 365, 899	647, 400 263, 220	2, 192, 510 546, 119	779, 80 422, 63
Wyoming Undistributed 3	1, 353, 178		1, 181, 000		1, 836, 713		4, 813, 000	
	146, 389, 536	30, 827, 822	18, 022, 000	13, 942, 000	60, 874, 506	[45 <b>,</b> 193, 937	104, 806, 000	21, 004, 0

Sand and gravel sold or used by commercial and Government-and-contractor producers in the United States in 1942, by States and uses—Continued

		Gravel—C	ontinued			Sand and	gravel	
State	Railroad	ballast 6	Oth	ier 7	Total co	mmercial		vernment- ntractor
	Short	Value	Short tons	Value	Short tons	Value	Short tons	Value
Alabama	(1)	(1)	39, 975	\$31, 278	4, 039, 335	\$2, 500, 277	620, 289	
Arizona		\$5, 881	7,055	2, 577	533, 796	491, 267	1, 077, 557	702, 33
Arkansas	525, 836		12, 025	14, 321	3, 856, 567	2, 860, 593	1, 975, 300	1, 058, 61
California	663, 224	160, 187	316, 409	149, 843	23, 730, 152	16, 336, 954	11, 061, 822	5, 730, 05
Colorado		160, 187 14, 987	371	456		1, 318, 817	2, 748, 988	1, 901, 88
Connecticut	26, 630	6, 658	131, 613	25, 157	2, 443, 809	1, 539, 276	516, 668	71, 30
Delaware					169, 267	95, 298		<b> </b>
Florida	(1)	(1)			1, 834, 863	1, 339, 361		(1)
Jeorgia	l				969, 934	732, 528	(1)	
daho	624, 225	74, 707	(1)	(1)	1, 908, 917	1, 455, 884	1, 209, 664	527, 17
llinois	2, 472, 013	1, 061, 628	95, 412			10, 675, 579	1, 181, 427	857, 26
ndiana owa	1, 656, 968		841, 173	353, 065			496, 465	200, 68
Owa	246, 573	93, 189 (¹)	8, 567 23, 657	19, 155 34, 583	3, 439, 816 4, 386, 182	1, 800, 955	3, 260, 929	389, 49 393, 21
Kansas Kentucky	200, 162	89, 565	20, 007	34, 383	2, 059, 570	2, 380, 064 1, 602, 163	814, 818 344, 065	393, 21
ouisiana	429, 734	269, 569	9, 580	9, 764	4 542 406	3, 534, 215	72, 922	141, 53 17, 53
Maine.	124 216	47, 237	37, 099	31, 395	4, 542, 496 1, 147, 203	529, 499	1, 102, 051	270, 64
Maryland Massachusetts	121,210	1., 20.	01,000	01,000	5, 630, 760	5, 517, 370	309, 363	30,06
Massachusetts	55, 880	21, 363	281, 917	87, 570	5 179 419	3 105 674	(1)	(1)
Michigan	551,688	208, 777	38, 407	12, 382	11, 938, 226	6, 306, 901	(1) 3, 604, 715	1, 055, 33
Minnesota	1, 864, 356 408, 746	208, 777 555, 991	523, 591	78, 392	11, 938, 226 5, 332, 428 2, 703, 772	2, 063, 883	5, 568, 065	538, 44
Mississippi	408, 746	144, 506	5, 387	3, 082	2, 703, 772	1, 588, 836	553, 779	177, 53
Missouri	233, 928	133, 630	3, 667	2,098	3, 868, 719	2, 584, 878	621, 931	347, 04
Montana	1, 250, 066	383, 245	135, 080	20, 162	3, 970, 353	2, 371, 627	1, 275, 889	614, 84
Vebraska	31, 306	10, 906	(1)	(1) (1)	6, 166, 840	3, 119, 463 758, 720	360, 825	122, 15
Vevada	608, 865	176, 165	(1)	(1)	1, 290, 843 79, 718	758, 720	1, 445, 016	749, 75
New Hampshire			16-000		79, 718	66, 076	1, 207, 676	92, 98
New Jersey New Mexico	(1)	(1)	16, 000	22, 167	6, 018, 200 261, 358	5, 725, 586	14,778	$^{1,27}_{(1)}$
New York	100, 836	62, 453	114, 070	135, 723	13, 592, 399	146, 866 9, 518, 598	2, 692, 968	2, 322, 64
North Carolina	34, 420	27, 335	(1)	(1)	3, 325, 816	2, 279, 424	2, 692, 968 954, 382	2, 322, 64 212, 39
North Dakota	425, 287	111, 523	80, 945	13, 088	695, 079	274, 520	1, 814, 605	69, 09
Ohio	1, 496, 896	712, 196	197, 853	265, 048	13, 303, 442	10, 465, 498	449, 951	105, 39
Oklahoma	35, 207	10, 629	51, 469	68, 469	1, 690, 169	1, 202, 996	1, 419, 461	743, 64
Oregon	304, 995	173, 164	187, 820	87, 794	5, 019, 306	3, 562, 369	1,641,005	935, 14
Pennsylvania			38 <b>, 3</b> 03	23, 498	10, 472, 568	10, 666, 745	141, 843	33, 99
Puerto Rico							(1)	(1)
Puerto Rico			2, 823	1,045	415, 193	318, 292	157, 244	<b>4</b> 3, 58
outh Caronna	21,000	4, 306	289	318	647, 483	304, 644	82, 060	50, 52
outh Dakota		83, 124	22, 959	2, 249	1, 952, 460	1, 123, 547	1, 625, 523	320, 36
Cennessee	(1) 1, 567, 766	(1)	7, 213	3, 599	3, 550, 427	3, 086, 499	(1) 4, 035, 273	(1)
Cexas	1, 007, 700	628, 429 87, 058	30, 652	33, 843	13, 692, 698	10, 116, 046 1, 697, 946	4, 035, 273	1, 523, 36
Vermont	506, 877 14, 021	2, 572	(1)	(1)	3, 012, 009 112, 756	1, 097, 946	862, 832	381, 35
/irginia	00 227	160, 627	(1)	(1)	5, 219, 534	48, 689 5, 378, 848	363, 575 391, 219	124, 56 81, 38
Vashington	1, 011, 548	309, 615	280, 996	85, 168	5, 634, 676	3, 133, 486	2, 537, 874	961, 41
Vest Virginia	62, 230	43, 442	200, 000	50, 100	2, 842, 547	3, 580, 973	216, 331	166, 37
Visconsin	1 659 965	329, 399	180, 096	33, 872	6, 204, 730	2, 527, 413	3, 060, 782	969, 20
Vyoming	2, 678, 682	687, 472	7, 276	3, 763	3, 421, 078	1, 182, 888	557, 595	₹ 430, 51
Vyoming Undistributed 2	625, 943	360, 292	43, 077	20, 421		-, 20 <b>-, 3</b> 00	6, 949, 000	3, 569, 00
						159, 427, 273		

Included under "Undistributed."
Includes items entered as (1).
Includes items entered as (1).
Includes 422,922 tons of blast sand valued at \$1,071,018.
Includes 39,352 tons of ballast sand valued at \$8,740, produced by railroads for their own use.
Includes 178,191 tons of sand valued at \$27,500, used by railroads for fills and similar purposes.
Includes 10,243,680 tons of ballast gravel valued at \$2,031,339, produced by railroads for their own use.
Includes 1,294,861 tons of gravel valued at \$141,917, used by railroads for fills and similar purposes.

Government-and-contractor production.—Reflecting the changing pattern of activity in the industry, Government-and-contractor production of sand and gravel in 1942 was 33 percent lower than in 1941. State governmental agencies reported 33 percent of the total, counties 26, municipalities 2, and other agencies (principally Federal organizations) 39 percent. An outstanding development was the continued decrease in direct production by governmental agencies, as indicated by the fact that contractors contributed 48 percent of the total in 1942 compared with 38 percent in 1941 and 27 percent in 1940. State agencies reported that contractors supplied them with 52 percent of their requirements in 1942.

Average value per ton of contractor tonnage increased considerably, but material produced by construction and maintenance crews was valued only slightly higher than in 1940 and 1941. Other details are

shown in the following tables.

Sand and gravel sold or used by Government-and-contractor producers in the United States, 1938-42, by uses

		San	đ		Gravel					ntractor
Year	Buil	ding	Pav	ing	Buil	ding	Pav	ing	sand and	l gravel
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
1939_ 1940_	5, 815, 000 5, 149, 000	2, 255, 000 2, 039, 000	9, 114, 000	2, 767, 000	9, 866, 000	4, 922, 000	82, 442, 000	22, 690, 000	75, 560, 447 107, 615, 000 107, 052, 000 107, 159, 000 71, 399, 000	32, 418, 000 32, 500, 000

Sand and gravel sold or used by Government-and-contractor producers in the United States, 1939-42, by types of producers

	1939		1940		1941		1942	
Type of producer	Short tons	Average value per ton	Short tons	Aver- age value per ton	Short tons	Aver- age value per ton	Short tons	Average value per ton
Construction and mainte- nance crews	71, 934, 000 35, 681, 000	\$0. 29 . 39		\$0. 28 . 37				<b>\$</b> 0. 29
	107, 615, 000	. 32	107, 052, 000	. 30	107, 159, 000	. 30	71, 399, 000	. 41
States Counties Municipalities Other agencies	35, 770, 000 16, 588, 000 2, 093, 000 53, 164, 000	.21	21, 685, 000 1, 923, 000	.22	22,772,000 1,637,000	.20	18,841,000 1,397,000	.21
	107, 615, 000	. 32	107, 052, 000	. 30	107, 159, 000	.30	71, 399, 000	.4

# METHOD OF TRANSPORTATION

Despite adverse conditions, such as rubber and gasoline shortages, trucks transported the major part of all sand and gravel produced in 1942. Railroads were second in importance, handling nearly half of the output of commercial operations. Waterways furnished minor but locally important facilities.

Sand and gravel sold or used by commercial producers in the United States, 1941-42, by methods of transportation <sup>1</sup>

	194	1941		1942		
Method of transportation	Short tons	Percent of total reported	Short tons	Percent of total reported		
Truck Rail Waterway	74, 452, 542 69, 225, 395 22, 201, 899	44.9 41.7 13.4	103, 777, 190 93, 456, 656 21, 603, 759	47. 4 42. 7 9. 9		
Total reported Percent of total commercial production covered	165, 879, 836	100. 0 91. 0	218, 837, 605	100. 0 94. 0		

<sup>&</sup>lt;sup>1</sup> For practical purposes the entire output of Government-and-contractor operations commonly is moved by truck. Including Government-and-contractor production, sand and gravel moved as follows—1941: Truck 60 percent, rail 25 percent, and waterway 8 percent; 1942: Truck 60 percent, rail 32 percent, and waterway 8 percent.

## DEGREE OF PREPARATION

Refinements in the technology of the various consuming industries have advanced to a point that preparation was required for 72 percent of the sand and gravel used in 1942. Part of this high percentage is due to reduced consumption in many public projects that require only bank-run material, but the proportion of prepared material has not been under 59 percent during the past 5 years. As shown in the accompanying table, most of the prepared material is supplied by commercial operations, and this largely explains the fact that the average value per ton reported by commercial producers is appreciably higher than that from Government-and-contractor operations.

Sand and gravel (prepared or unprepared) sold or used by producers in the United States, 1941-42, by commercial and Government-and-contractor operations

•		1941		- 1	1942				
	Quant	tity	Average	Quant	ity	Average			
	Short tons Percent Per ton		Short tons	Percent	value per ton				
Commercial operations: Prepared Unprepared	159, 784, 239 21, 772, 228	88 12	\$0.67 .33	200, 131, 369 32, 816, 418	86 14	\$0. 73 . 38			
Covernment and a set of the set	181, 556, 467	100	. 63	232, 947, 787	100	. 68			
Government-and-contractor oper- ations: Prepared Unprepared	22, 311, 000 84, 848, 000	21 79	. 49 . 25	20, 076, 000 51, 323, 000	28 72	. 67 . 30			
	107, 159, 000	100	. 30	71, 399, 000	100	. 41			
Grand total	288, 715, 000		. 51	304, 346, 000		. 62			

## SIZE OF PLANTS

The average commercial sand and gravel plant is a comparatively small operation. Approximately half of the plants produce less than 25,000 tons per year, and the average output per plant in this group was about 8,100 tons in 1942. Only 23 percent of the producers reported more than 100,000 tons in 1942 but they supplied 78 percent of the total tonnage. Details of output, by size groups, for 1941 and 1942 are given in the following table.

Comparison of number and output of commercial sand and gravel plants in the United States, 1941-42, by size groups 1

			1941				1942	
	Plai	nts 3	Producti	ion	Pla	nts 3	Producti	ion
Size group in short tons		72.5		1				15.
	Num- ber	Per- cent of total	Short tons	Per- cent of total	Num- ber	Percent of total	Short tons	Per- cent of total
Less than 25,000	1, 104 390	48. 5 17. 1	9, 404, 000 13, 902, 000	5. 5 8. 1	1, 258 366	49. 2 14. 3	10, 225, 000 13, 139, 000	4. 6 5. 9
50,000 and less than 100,000 100,000 and less than 200,000	331 227	14. 6 10. 0	23, 168, 000 31, 778, 000	13. 4 18. 4	336 299	13. 1 11. 7	24, 591, 000 42, 193, 000	11. 1 19. 1
200,000 and less than 300,000	96	4.2	23, 212, 000	13.4	132	5. 2	32, 312, 000	14.6
300,000 and less than 400,000 400,000 and less than 500,000	47 29	2.1 1.3	16, 642, 000 12, 867, 000	9. 6 7. 5	56 34	2. 2 1. 3	19, 361, 000 14, 981, 000	8.7 6.8
500,000 and less than 600,000 600,000 and less than 700,000	16 8	.7	8, 880, 000 5, 106, 000	5. 1 3. 0	24 14	1.0	13, 046, 000 8, 918, 000	5. 9 4. 0
700,000 and less than 800,000	10	.4	7, 526, 000	4.4	12	. 5	8, 972, 000	4.1 1.9
800,000 and less than 900,000 900,000 and less than 1,000,000	5 4 7	.2	4, 186, 000 3, 734, 000	2.4 2.2	5 3 18	.2 .1 .7	4, 112, 000 2, 819, 000	1.3
1,000,000 and over	2,274	100.0	12, 068, 000 172, 473, 000	7.0	2,557	100.0	26, 523, 000 221, 192, 000	12.0

<sup>&</sup>lt;sup>1</sup> Plants operated by or for States, counties, and municipalities are not included; also not included are approximately 187 railroad plants with an output of 9,083,000 tons of sand and gravel in 1941, and 172 plants with an output of 11,756,000 tons in 1942.

<sup>2</sup> Includes a few companies operating more than 1 plant but not submitting separate returns for individual

#### PRINCIPAL TRENDS

Sand and gravel for construction.—Over 90 percent of the sand and gravel marketed in the United States is absorbed by the construction industries for use in building and paving and as railroad ballast. Figure 2 shows the correlation between total construction activity, concrete-pavement contract awards, sales of sand, and sales of gravel. Production of these commodities has expanded greatly in satisfying the demands of the tremendous military and civilian construction programs of the rearmament period. During the latter part of 1942 the rate slowed down appreciably as many projects reached completion; and with the curtailment of private building, highway construction and maintenance, and public works programs, all signs point to a reduced output of sand and gravel in 1943.

Industrial sands.—Sand has many important uses in the manufacturing industries. Glass and molding sands are practically indispensable in their fields; and others, like filter, engine, and abrasive sands, perform vital functions. Except for filter and grinding and polishing sands, production of all the industrial sands was greater in 1942 than in 1941. Owing to the fact that these sands enter directly into the manufacturing and operational processes, their volume undoubtedly will be better-maintained throughout the wartime period than will the construction sands. Figures 3 and 4 show graphically details of production of these sands in past years, and their correlation with indexes of industrial production.




FIGURE 2.—Value of sand and gravel production compared with total construction (value) and concrete pavements (contract awards, thousands of square yards) in the United States, 1933-42. Data on construction and concrete pavements from Bureau of Foreign and Domestic Commerce.

#### EMPLOYMENT AND PRODUCTIVITY

In 1941 employment in the commercial sand and gravel industry reached the highest level since the Bureau of Mines began recording manpower information in 1933.<sup>2</sup> Operators who produced about four-fifths of the total tonnage reported employment data for 1941, and from this information it is apparent that approximately 25,000 men were employed in the industry in that year. The number and length of the working days increased, and average output per manhour reached a record high—12 percent above the 1940 performance.

Employment in the commercial sand and gravel industry, sand and gravel produced at plants included in the study, and average output per man in the United States, 1936-41 1

			Employm	ent		Pro	duction		
			Time e	mployed					Per- cent
Year Average				Ma	n-hours	Com- mercial	Average per man (short tons)  Per shift Per hour		of com- mer-
rear	ber of num-	num- ber of	Total man- shifts	Average per man per day	Total	sand and gravel (short tons)			cial indus- try repre- sented
1936	16, 127 16, 062 14, 971 15, 617 16, 595 19, 909	207 215 201 214 217 228	3, 332, 532 3, 458, 994 3, 001, 796 3, 335, 321 3, 596, 886 4, 530, 488	8. 6 8. 6 8. 5 8. 4 8. 4 8. 6	28, 672, 615 29, 754, 746 25, 578, 807 28, 054, 960 30, 263, 744 38, 978, 128	95, 219, 468 97, 113, 001 81, 742, 896 96, 755, 364 101, 143, 305 144, 594, 925	28. 6 28. 1 27. 2 29. 0 28. 1 31. 9	3.3 3.3 3.2 3.5 3.3 3.7	83. 8 81. 8 81. 1 81. 7 77. 1 79. 6

<sup>&</sup>lt;sup>1</sup> Excludes plants operated by or directly for States, counties, municipalities, and other Government agencies.

<sup>&</sup>lt;sup>2</sup> See Minerals Yearbook: 1935, pp. 941–943; 1936, pp. 843–845; 1940, Review of 1939, pp. 1218–1221; Review of 1940, pp. 1191–1193; and 1941, pp. 1285–1286.

Productivity data for 1941, by regions, are summarized in the accompanying table. Outstanding is the fact that production efficiency improved in every district except one in which the same rate




FIGURE 3.—Production of industrial sands in the United States, 1916-42.




FIGURE 4.—Trends in production of molding sand compared with industrial production and output of steel ingots, 1933-42. Index of industrial production from Federal Reserve Board; statistics of steelingot production compiled by American Iron and Steel Institute.

was maintained as in the previous year. Many of the increases were substantial, the average being 0.4 ton per man-hour for the entire country. That this improvement represents a legitimate gain in efficiency is indicated by the fact that the degree of preparation of the material was exactly the same in both years.

Employment in the commercial sand and gravel industry, sand and gravel produced at plants included in the study, and average output per man in the United States in 1941, by regions 1

		498	Employme	nt		Pro	duction	esto Julius N	+
			Time (	mploy	red			rage	Per cent
Region	Aver-			М	an-hours	Com- mercial	(sh	per man (short tons)	
	num- ber of men	Aver age num ber o days	Total man- shifts	Average per man per day	Total	sand and gravel (short tons)	Per shift	Per hour	cial indu try repre sente
Maine, New Hampshire, Vermont, Rhode Island, Massachusetts, and Con-									
necticut New York Pennsylvania, New Jersey.	871 1, 716	195 221	170, 001 378, 749	8. 5 8. 2	1, 446, 209 3, 119, 059	6, 676, 116 12, 928, 933	39. 27 34. 14	4.6 4.1	84. 86.
and Delaware West Virginia Virginia	2, 652	253	671, 446	8.6	5, 754, 129	16, 236, 508	<b>24</b> . 18	2.8	98.
Maryland, and District of Columbia South Carolina, Georgia, Alabama, Florida, and	1, 348	273	367, 427	8.8	3, 217, 086	7, 072, 345	19. 25	2. 2	62.
Mississippi North Carolina, Kentucky	945	240	226, 510	9.3	2, 103, 546	6, 440, 520	28. 43	3.1	89.
and Tennessee	1, 189	<b>25</b> 8	306, 313	8.6	2, 639, 469	7, 088, 487	23. 14	2.7	89.
Texas Ohio Illinois and Indiana	1, 561 1, 615 1, 859	241 227 211	376, 645 367, 243 391, 935	9. 5 8. 4 8. 5	3, 560, 274 3, 090, 599 3, 318, 939	9, 043, 365 9, 684, 943 18, 193, 467	24.01 26.37 46.42	2. 5 3. 1 5. 5	59. 81. 83.
Michigan and Wisconsin North Dakota, South Da- kota, and Minnesota	1, 288	203	261, 359	8.7	2, 267, 998	12, 420, 760	47. 52	5. 5	76.
Nebraska and Iowa Kansas, Missouri, and Okla-	376 698	149 176	56, 190 <b>123,</b> 067	8. 4 9. 2	474, 087 1, 137, 810	2, 817, 243 4, 446, 114	50, 14 36, 13	5. 9 3. 9	52. 80.
homa Wyoming, Colorado, New Mexico, Utah, and Ari-	920	228	209, 452	8.7	1, 813, 125	7, 101, 317	33. 90	3.9	92.
zona California and Nevada Montana, Washington, Ore-	401 1, 616	172 250	69, 004 403, 626	8. 3 8. 1	575, 288 3, 256, 232	2, 887, 650 16, 123, 634	41.85 39.95	5. 0 5. 0	77. 81.
gon, and Idaho	854	177	151, 521	7. 9	1, 204, 278	5, 433, 523	35. 86	4.5	64.
Total United States.	19, 909	228	4, 530, 488	8.6	38, 978, 128	144, 594, 925	31. 92	3.7	79. (

<sup>&</sup>lt;sup>1</sup> Excludes plants operated by or directly for States, counties, municipalities, and other Government agencies.

## **PRICES**

The ton values of every class of sand and gravel were higher in 1942 than in 1941.

Increases in ton value averaging 54.8 percent for sand and 33.3 percent for gravel were registered for the output of Government-and-contractor operations. Smaller but substantial gains, averaging 7.6 percent for sand and 8.2 percent for gravel, were made by commercial operations. Additional statistical details covering total and ton values of the various classes of sand and gravel are contained in the table accompanying the summary outline at the beginning of this chapter.

Prices of sand and gravel were under the jurisdiction of the Office of Price Administration, and on May 11 the General Maximum Price

Regulation froze prices at the maximum levels existing in March 1942. Subsequently the Office of Price Administration authorized upward revision of prices in a very few individual instances, but no general increases were approved.

#### **NEW DEVELOPMENTS**

Although molding-sand technology has been developing for hundreds of years in the metal industries, new attention is being directed to the subject owing to the complex problems of handling magnesium in the molten condition. The great expansion of magnesium-production facilities in 1942 stimulated interest and research, and technical articles explaining modern practice appeared.3

Before the war industrial sands from Belgium found a market in the Pacific Northwest, and a substantial tonnage enters this area from California, Illinois, and other distant States. In an attempt to determine the possibilities of developing local supplies of glass and molding sands, silica deposits in the State of Washington were in-

vestigated. A report on the subject was published.<sup>4</sup>
During recent peacetime years the Work Projects Administration has been an influential factor in the sand and gravel industry. On December 4, 1942, the President directed that, since increase in private employment had made the work-relief program no longer necessary, liquidation of project operations should be completed as soon as By taking this action it was expected that no project funds need be provided for the next fiscal year.

In spite of priority restrictions, many new plants were built in 1942, but most of them were comparatively small portable or temporary operations. Many producers whose permanent plants are well located to furnish civilian requirements compensated for a serious drop in this volume by operating temporary plants at other locations to

serve war-construction demands.5

## FOREIGN TRADE 6

Even in peacetime years only minor quantities of sand and gravel were imported or exported. For example, during the period 1937 to 1939 imports averaged about 0.25 percent of domestic production and exports only about 0.02 percent. Foreign trade statistics for the 10-year period 1932-41 are shown in the accompanying table. Owing to wartime restrictions, no figures on current foreign trade can be published, but it is apparent from the data on sand and gravel recorded herein that their absence will not detract appreciably from the value of the report, particularly in view of the recent rigid restrictions on foreign movement of commodities. Foreign trade figures will be released at the termination of the present war emergency to preserve the continuity of the statistical record.

<sup>&</sup>lt;sup>3</sup> Cramer, Eugene M., Rapid Methods of Analysis for Sand Control in Magnesium Foundries: Am. Foundryman, vol. 4, No. 12, 1942, pp. 11-12.

<sup>4</sup> Wilson, Hewitt, Skinner, Kenneth G., and Couch, Albert H., Silica Sands of Washington: University of Washington Exp. Sta. Bull. 108, 1942, 80 pp.

<sup>8</sup> Pit and Quarry, Sand and Gravel: Vol. 35, No. 7, January 1943, pp. 77-83.

<sup>6</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Sand and gravel imported for consumption in the United States, 1932-41, by classes

	Glass	sand 1	Other	sand 2	Gra	avel	212, 458 120, 566 109, 54	
Year	Short tons	Value	Short tons	Value	Short tons	Value		Value
1932 1933 1934 1935 1936 1936 1937 1938 1939 1939 1940	26, 574 26, 275 24, 516 44, 291 52, 944 51, 090 33, 889 23, 690 4, 337	\$51, 016 57, 682 46, 094 94, 966 117, 706 79, 112 68, 315 33, 604 8, 722	140, 793 61, 597 36, 016 62, 225 124, 013 319, 134 611, 468 192, 106 264, 170 166, 228	\$94, 728 42, 155 33, 635 51, 658 62, 193 134, 430 157, 992 79, 272 90, 350 73, 229	45, 091 32, 694 74, 758 63, 189 201, 398 163, 406 55, 619 60, 147 175, 558 98, 748	\$18, 717 9, 707 18, 286 15, 851 38, 142 36, 193 22, 902 8, 399 25, 686 15, 387		\$164, 46 109, 54 98, 01 162, 47 218, 04 249, 73 249, 20 121, 27 124, 75 88, 61

<sup>1</sup> Classification reads "Sand containing 95 percent silica and not more than 0.6 percent oxide of iron and suitable for manufacture of glass."

<sup>2</sup> Classification reads "Sand, n. s. p. f."

3 January-September.

# Sand and gravel exported from the United States, 1932-41

Year	Short tons	Value	Year	Short tons	Value
1932	96, 015	\$211, 558	1937	67, 141	\$80, 197
1933	82, 453	54, 557		35, 572	30, 303
1934	33, 550	41, 649		27, 746	31, 931
1935	37, 393	26, 369		(2)	(2)
1936	49, 906	58, 453		(2)	(2)

Classification reads "Gravel and building stone."
 Not separately classified.

#### BLAST-FURNACE SLAG

The National Slag Association, continuing a policy begun in 1938, conducted a canvass of the 31 companies in the United States that prepare iron blast-furnace slag for commercial uses. The total output of air-cooled screened and unscreened and water-granulated slag for 1942 was 19,122,718 short tons, compared with 14,678,266 tons Sales of air-cooled slag were 19 percent greater in 1942 than in 1941, and the average value per ton was 1 cent lower.

Air-cooled slag was used principally in the construction and maintenance of highways, access roads, airport runways, defense plant and housing projects, and miscellaneous structures; as railroad ballast; and for sewage trickle filters. Other uses and quantities involved are shown in the accompanying table.

Nearly all the commercial output is produced east of the Mississippi River, chiefly at steel centers in Ohio, Alabama, Pennsylvania, and Illinois. Shipments, however, are made into all States east of the Mississippi, except some of the New England States outside the economic range of sources of supply. Shipments of slag are made by railroad, truck, and waterway. The following tabulation shows the pattern of distribution during the past 3 years.

# Shipments of commercial slag in the United States, 1940-42, by methods of transportation <sup>1</sup>

[Percent of total]

	Method of transportation	1940	1941	1942
Rail		55	55	52
Truck		 44	43 2	47 1
Water way		 		

<sup>1</sup> National Slag Association.

The average shipping range of blast-furnace slag in 1942 was 52 miles by rail, 17 by truck, and 117 by waterway. In most instances shipments did not exceed 140 miles by railroad, 35 by truck, and 160

by waterway.

During the process of crushing and screening blast-furnace slag, particles of metallic iron that escape through the slag notch of the blast furnace are recovered at the slag plant by hand picking and magnetic pulleys. During 1942 the companies surveyed reported 165,679 tons of metallic iron recovered and returned to the furnaces to bolster the supply of metal so vitally needed in the prosecution of the war. The yield slightly exceeds 1.2 percent or approximately 24 pounds of metallic iron per short ton of slag processed.

Not including those assigned to administrative, office, and sales activities, 1,629 plant and yard employees were engaged in producing commercial slag in 1942. The total number of man-hours in pro-

duction was 4,168,539.

Air-cooled blast-furnace slag sold or used by producers in the United States, 1941-42, by States <sup>1</sup>

		1941		1942			
State	Quan	tity		Quan			
	Short tons	Percent of total	Value	Short tons	Percent of total	Value	
AlabamaOhioPennsylvaniaOther States <sup>2</sup>	3, 698, 379 4, 239, 924 1, 667, 252 3, 564, 026	28. 1 32. 2 12. 6 27. 1	\$2, 528, 633 4, 000, 074 1, 564, 823 2, 730, 739	3, 936, 500 4, 492, 497 2, 522, 437 4, 714, 073	25. 1 28. 7 16. 1 30. 1	\$2, 793, 924 4, 080, 896 2, 354, 024 3, 488, 004	
	13, 169, 581	100.0	10, 824, 269	15, 665, 507	100.0	12, 716, 848	

National Slag Association.
 Illinois, New York, Maryland, Michigan, West Virginia, Kentucky, Colorado, Tennessee, and Massachusetts.

# Blast-furnace slag sold or used by producers in the United States in 1942, by uses 1

	S	creened	Unscreened			Granulated			
<b>Use</b>		Valu	Value		Val	ue		Value	
	Short tons	Total	Aver- age per ton	Short tons	Total	Aver- age per ton	Short tons	Total	Aver- age per ton
Concrete (pavements, buildings, bridges, etc.)	6, 591, 722 2, 995, 045 205, 966 247, 736 63, 236	212, 547 331, 560 45, 702	. 92 . 67 1. 03 1. 34	396, 930	\$626, 729 125, 289 103, 016	.36	2, 737, 469	\$453, 156	\$0. 17
Sewage trickle filter. Airport runways. Parking lots and private driveways. Agricultural purposes Cement manufacture. Glass manufacture. Concrete products Other uses.	11, 716	921, 838 97, 650 17, 971 17, 257 20, 217	. 93 . 97 1. 00 1. 47 . 95	78, 097		.37	17, 890 701, 852	14, 046 119, 892	
Total: 1942	12, 372, 218 8, 132, 396	7, 015, 616 5, 870, 582	.84 .86 .83	2, 073, 611 797, 363 1, 230, 832 812, 220 1, 202, 754	390, 082 507, 288 361, 554	. 49 . 41	1, 188, 094	239, 833 257, 737 122, 017	. 17 . 16 . 26 . 10 . 12

<sup>&</sup>lt;sup>1</sup> National Slag Association.

# **GYPSUM**

By Forrest T. Moyer and M. G. Downey

## SUMMARY OUTLINE

	Page		Page
Summary	1283	Distribution of sales, by uses	1289
Salient statistics	1284	Prices	1293
Domestic production	1287	Recent developments	1293
Calcined production and equipment of proc-		Foreign trade	1294
essing plants		World production	1295

#### SUMMARY

The complete swing from peacetime to wartime construction in 1942 affected the gypsum industry adversely and general activity declined sharply. The over-all decrease in operations from 1941 may declined sharply. be measured by the 17-percent drop in new crude supply to a total of 5,099,084 short tons and the 24-percent slump in production of calcined gypsum to 3,045,082 tons in 1942. Markets for gypsum products were affected in diverse ways. Sales volumes of most products declined markedly from 1941, but these declines were compensated in part by the strong demand for cement retarder, agricultural gypsum, wallboard, and sheathing, of which sales advanced to record volumes in 1942. In addition, markets for laminated-board products expanded phenomenally after their introduction about the middle of the year. Principally as a result of the brisk demand for certain of the more highly processed, prefabricated products that command a higher price than other gypsum materials, the value of total sales by the industry declined only 9 percent from the record set in 1941 to a total of \$63,170,744 in 1942. Although labor and material costs increased, prices of most gypsum products in 1942 were relatively unchanged from the levels that have prevailed in recent years. General Maximum Price Regulation of the Office of Price Administration, effective May 11, froze prices of gypsum products at the highest selling value, f. o. b. mill, obtained during March 1942. Effective August 1, Maximum Price Regulation 188 of the same agency removed gypsum products from the general regulation and continued the March prices as maximum.

War controls on building construction by the Federal Government were the primary causes of the marked selectivity in demand for gypsum building products. The stoppage of nonessential public and private building by War Production Board Conservation Order L-41 of April 9 had an immediate effect upon the industry, and sales of lath, tiles, and nearly all building plasters slumped sharply after the first quarter of the year. The more restrictive revision of this order on September 7 and the establishment of review committees in War Production Board on October 22 to pass on essentiality of current and proposed construction both had adverse effects on sales of these

1283

products. On the other hand, the joint War Housing Construction Standards of National Housing Agency and War Production Board of October 28 prohibited the use of lumber for housing when suitable substitutes were available and thus enlarged the markets for gypsum wallboard, sheathing, and laminated board.

Salient statistics of the gypsum industry in the United States, 1938-42

	1938	1939	1940	1941	1942
A ctive establishments 1	90	.92	91	93	92
Crude gypsum 2— Mined short tons Imported do	2, 684, 205 789, 429	3, 226, 737 1, 308, 078	3, 699, 015 1, 405, 210	4, 788, 534 1, 347, 957	4, 697, 568 401, 516
Apparent supplydo	3, 473, 634	4, 534, 815	5, 104, 225	6, 136, 491	5, 099, 084
Calcined gypsum produced: 3 Short tons Value	2, 252, 878 \$10, 989, 626	2, 881, 269 \$14, 620, 597	3, 307, 709 \$17, 254, 667	3, 980, 567 \$19, 746, 914	3, 045, 082 \$16, 403, 068
Gypsum products sold: 3 Uncalcined uses:					
Short tons	756, 565 \$1, 681, 371	867, 782 \$1, 927, 415	929, 119 \$2, 250, 857	1, 320, 713 \$3, 138, 958	1, 514, 913 \$3, 533, 607
Short tons	94, 248 \$1, 154, 517	110, 395 \$1, 373, 564	123, 643 \$1, 532, 738	151, 960 \$1, 885, 313	142, 705 \$1, 840, 927
	\$33, 420, 420	\$42, 627, 260	\$49, 709, 049	\$64, 734, 171	\$57, 796, 210
Total value	\$36, 256, 308	\$45, 928, 239	\$53, 492, 644	\$69, 758, 442	\$63, 170, 744
Gypsum and gypsum products— Imported for consumption————————————————————————————————————	\$1,002,001 \$282,782	\$1, 363, 967 \$309, 453	\$1, 429, 289 \$264, 128	\$1, 282, 140 \$529, 574	\$517, 071 \$977, 863

<sup>1</sup> Each mine, plant, or combination mine and plant is counted as 1 establishment.

Excludes byproduct gypsum.
 Made from domestic, imported, and byproduct crude gypsum.

The outstanding feature of the industry in 1942 was the steadily increasing demand for wallboard, sheathing, and the new laminatedboard products. All of these are well-adapted to the current types of small, low-cost war and military housing which require prefabricated materials that are not high-priced and are quickly and easily erected with a minimum of labor. Although the advantages of these products would have assured a fair share of the market, the serious shortage of lumber undoubtedly helped increase demand for gypsum boards. Moreover, sheathing and laminated boards entered new fields of application, principally in nonresidential building, and were used widely as exterior siding and roof decks. For exposure to weather these products now are available with a variety of weather-resistant surfacing materials ranging from granule-coated asphalt roofing to a mill-painted finish. Laminated boards reportedly were accepted as satisfactory materials for farm construction work on which war controls were less restrictive than on housing. The effect of these factors was a 38-percent increase over 1941 in square footage of wallboard and a 110-percent gain in area of sheathing sold. The active demand for laminated products after their introduction in May 1942 is shown by sales of 53,170 M square feet (in terms of area of component board and not of finished product) valued at nearly 11/2 million dollars.

In marked contrast to the record consumption of finished prefabricated gypsum building products, sales of the built-in materials—lath, tiles, and building plasters—fell sharply. In 1942 the square footage of lath sold was only half the record area sold in 1941, and the

long uptrend in demand for this product that started in 1934 was broken. Tile sales were more than one-fourth below and aggregate tonnage sales of building plasters (including Keene's cement) were 40 percent below 1941 volumes. Sales of "base-coat" and "gauging and molding" plasters, the important tonnage groups, slumped 45 and 39 percent, respectively, from the quantities sold in 1941. Indicated consumption increased only in the "insulating and roof-deck" group of building plasters, and sales were more than double the 1941 tonnage. This sharp gain reflects the high level of industrial building in which roof-deck plasters are used for poured-roof construction.




FIGURE 1.—Trends of new crude supply, domestic crude mined, and production of calcined gypsum. 1938-42, by quarters.

The source composition of the new crude supply in 1942 was changed markedly in that only 8 percent was derived from imports whereas in 1941 imported crude gypsum represented 22 percent of the total supply. Throughout 1942 the flow of crude from quarries in Nova Scotia and New Brunswick, Canada, to tidewater processing plants along the Atlantic coast was subject to Government war controls. Gypsum imports were placed on a quota basis, which was lowered drastically on January 21 and April 22. By August all company owned or leased gypsum boats had been requisitioned for other uses by the Federal Government or were lost at sea, and companies had great difficulty

in obtaining shipping space because of the relatively low preference rating assigned to gypsum. As a result crude imports in the last 4 months of 1942 were a mere trickle compared with normal volumes. and the total for the year fell 70 percent below the 1941 tonnage. In figure 1 the long-term trends of new crude supply and domestic crude mined show a marked discordance between the fourth quarters of 1939 and 1942. It is evident that the rate of imports advanced sharply in the October-December period of 1939 and continued at a relatively high level through the fourth quarter of 1941. advanced rate probably represented efforts by importers to build up stocks in this country after the outbreak of war in Europe in September The marked parallelism in trends of new supply and calcined production throughout the 1938-42 period is notable. In 1942 convergence of the new-supply and domestic-crude curves and parallelism of the new-supply and calcined-production curves indicate that domestic material replaced imported crude chiefly in the markets for uncalcined products, although there undoubtedly was also some replacement in the calcined-products field.

The critical state of crude supplies at Atlantic tidal plants toward the end of 1942 was mitigated by the fact that the greater demand for gypsum products was in sections of the country not served from these plants. To help relieve the supply problem at importing plants in 1942, some domestic crude was shipped by barge from western New York to the New York City area, calcined gypsum from a domestic operation was moved by rail to a southern tidal plant, and the calcined output of a byproduct-gypsum plant was utilized in the New York City area. Total stocks of crude gypsum in the country on December 31, 1942, aggregated 741,549 short tons, of which 152,581 tons were at Atlantic tidewater plants. The only other recent stock data available are those for December 31, 1935, when there were two less calcining plants on Atlantic tidewater. At that time, stocks in the country totaled 668,927 tons, of which 178,919

tons were on the Atlantic coast. The Department of Justice in September 1942 nol-prossed its criminal suit against two gypsum companies for illegal control of perforated-lath prices. An earlier criminal action was settled by a directed verdict of acquittal in November 1941. Of the three original actions 1 only the civil suit charging seven gypsum companies and officials with violations of sections 1, 2, and 3 of the Sherman Antitrust Act Principal objectives of the civil action are to remains unsettled. restrain these companies and individuals from violating the act and to have certain patents and agreements declared void.

Wage increases during 1942 were reported by some gypsum operators in New York, Michigan, Iowa, Utah, Nevada, and California. Despite the decline in demand for many products, there was a labor shortage in the industry in nearly all sections of the country. shortage tended to increase operating costs, as producers were forced to overtime rates of pay to fill orders.

<sup>1</sup> United States of America v. Certain-teed Products Corporation et al., No. 66007, in the District Court of the United States for the District of Columbia, April term, 1940, 54 pp.

United States of America v. United States Gypsum Co. et al., No. 66008, in the District Court of the United States for the District of Columbia, April term, 1940, 22 pp.

United States of America, Plaintiff v. United States Gypsum Co. et al., Defendants, Civil Action No. 8017, in the District Court of the United States for the District of Columbia. Filed August 15, 1940, 127 pp.

The second secon

## DOMESTIC PRODUCTION

Total output from domestic gypsum mines in 1942 showed a smaller proportional decline than did other general measures of industry activity and was only 2 percent below the 1941 tonnage owing to the necessity of supplanting imported supplies along the east coast and a strong demand for gypsum products in far Western and some Midwestern States. Of the 17 producing States, production was higher than in 1941 in 6, lower in 10, and was resumed in Arizona after a lapse of 2 years. The ranking States were New York, Michigan, Iowa, and California. Active operations totaled 64, of which 29 were underground mines, 30 open quarries, and 5 mine-quarry combinations.

The average value of run-of-mine gypsum advanced 3 cents over the 1941 figure to \$1.45 per ton in 1942. As reported by producers this is a "plant" value, for little crude gypsum enters the open market. Data in the accompanying table relate only to natural gypsum and gypsite and do not include crude byproduct gypsum.

Crude gypsum mined in the United States, 1940-42, by States

	1940				1941		1942		
State	Active mines	Short tons	Value	Active mines	Short tons	Value	Active mines	Short tons	Value
California	6 3 8 5 4 9 3 7 4	259, 321 24, 641 487, 379 746, 982 250, 632 798, 229 176, 166 328, 261 45, 421 581, 983	\$437, 504 36, 787 587, 223 1, 017, 126 618, 050 1, 037, 181 227, 534 368, 882 60, 055 837, 568	7 (1) 8 5 4 9 3 7 4 13	381, 951 (1) 630, 930 805, 861 284, 795 1, 080, 320 258, 258 446, 419 61, 813 838, 187	\$618, 685 (1) 736, 185 1, 090, 309 754, 294 1, 500, 307 344, 489 467, 087 78, 147 1, 204, 720	9 (1) 7 6 5 10 3 6 4 14	426, 670 (1) 514, 587 891, 180 330, 333 1, 012, 987 243, 545 414, 196 48, 574 815, 496	\$662, 181 (1) 688, 211 1, 286, 242 540, 579 1, 605, 530 321, 652 496, 669 60, 259 1, 149, 857
	59	3, 699, 015	5, 227, 910	60	4, 788, 534	6, 794, 223	64	4, 697, 568	6, 811, 180

<sup>1</sup> Included under "Other States."

By groups of States as follows—1940: Kansas (2 active mines), Montana (2), South Dakota (1), and Wyoming (1)—197,703 tons valued at \$227,025; Ohio (2) and Virginia (2)—334,280 tons, \$610,543. 1941: Arkansas (1) and Kansas (2)—174,918 tons, \$177,499; Colorado (2), Montana (2), South Dakota (1), and Wyoming (1)—149,848 tons, \$222,710; Ohio (2) and Virginia (2)—513,421 tons, \$804,511. 1942: Arizona (1), Arkansas (1), and Kansas (2)—142,731 tons, \$170,403; Colorado (2), Montana (2), South Dakota (1), and Wyoming (1)—135,588 tons, \$202,612; Ohio (2) and Virginia (2)—537,177 tons, \$776,842.

# CALCINED PRODUCTION AND EQUIPMENT OF PROCESSING PLANTS

Production of calcined gypsum in 1942 dropped nearly one-fourth below kettle-and-kiln output in 1941 because of the slump in demand for building plasters after the first quarter of the year. In the 24 producing States 53 plants were active, of which 42 processed domestic crude, 10 imported crude, and 1 byproduct crude gypsum. Active calcining equipment in these plants comprised 172 kettles, 8 beehive kilns, 12 rotary kilns, and 4 grinding-calcining units. A canvass of the output of calcined gypsum by States was made for the first time for 1942; it showed the following distribution.

Calcined gypsum produced in the United States in 1942, by districts

District	Short tons	Value
New Hampshire, Vermont, Massachusetts, and Connecticut.  Eastern New York, New Jersey, Pennsylvania, Georgia, and Florida.  Western New York Ohio and Virginia Michigan and Indiana Iowa. Kansas and Oklahoma	91, 788 500, 011 529, 616 286, 296 424, 283 324, 387 159, 585	\$589, 055 3, 390, 693 2, 439, 984 1, 661, 865 2, 259, 095 1, 476, 107 853, 532
Texas Colorado, South Dakota, and Montana Utah California, Nevada, and Arizona	285, 430 73, 893 20, 695 349, 098	1, 202, 266 446, 562 122, 303 1, 961, 606
	3, 045, 082	16, 403, 068

Reflecting rising costs of labor, fuel, and materials, the average unit value of calcined gypsum, which is strictly a "transfer" value assigned by producers, increased 43 cents over the 1941 figure to \$5.39 per ton.

Active calcining plants and equipment in the United States, 1940-42, by States

	1940				-	19	941			19	42	
State Cal-		E	quipme	nt	Cal	Equipment		Cal	E	quipme	nt	
	cining plants	Ket- tles	Bee- hive kilns	Ro- tary kilns	Cal- cining plants	Ket- tles	Bee- hive kilns	Ro- tary kilns	Cal- cining plants	Ket- tles	Bee- hive kilns	Ro- tary kilns
California Iowa Michigan New York Texas Utah Other States 3	4 5 7 4 4 26	10 18 21 22 25 8 65	5 4	68	5 5 7 4 4 27	13 18 21 23 25 8 71	4 4	6	3 5 7 4 4 25	7 18 22 22 22 26 8 69	4 4	6
	55	169	9	1 17	57	179	8	3 17	53	172	8	<sup>2</sup> 16

<sup>&</sup>lt;sup>1</sup> Includes 3 grinding-calcining units.

The active demand for gypsum board kept the 36 board machines in the country working at a high rate throughout 1942. monthly survey conducted by the Bureau of Mines for the War Production Board show that the over-all rate of operations of all board machines was 84 percent of capacity in September, 89 percent in October, 80 percent in November, and 75 percent in December. Generally, machines in Atlantic tidewater plants were less active than those in plants processing domestic crude. In the latter group machines were operated at 93 percent of capacity in September, 97 percent in October, 87 percent in November, and 81 percent in De-These capacity data are on a time-utilized basis in which 100 percent equals full operation for 85 percent of the total number of hours in each month.

<sup>&</sup>lt;sup>1</sup> Includes 3 grinding-calcining units.
<sup>2</sup> Includes 4 grinding-calcining units.
<sup>3</sup> 1940: 1 calcining plant each in Arizona, Connecticut, Georgia, Indiana, Massachusetts, Nevada, New Hampshire, Oklahoma, Pennsylvania, South Dakota, Vermont, and Wyoming; 2 each in Colorado, Florida, Kansas, Montana, New Jersey, Ohio, and Virginia.
1941: 1 calcining plant each in Arizona, Connecticut, Georgia, Indiana, Massachusetts, New Hampshire, Oklahoma, Pennsylvania, South Dakota, Vermont, and Wyoming; 2 each in Colorado, Florida, Kansas, Montana, Nevada, New Jersey, Ohio, and Virginia.
1942: 1 calcining plant each in Arizona, Connecticut, Florida, Georgia, Indiana, Massachusetts, New Hampshire, Oklahoma, Pennsylvania, South Dakota, and Vermont; 2 each in Colorado, Kansas, Montana, Nevada, New Jersey, Ohio, and Virginia.

# DISTRIBUTION OF SALES BY USES

The marked changes from 1941 in distribution of total sales value among groups of products are traceable directly to differences in types of materials required for wartime compared with peacetime building. As shown in figure 2 the percentages represented by sales values of lath and building plasters (including Keene's cement) declined sharply from the 1941 distribution, whereas the value of all other boards (wallboard, sheathing, and laminated board) jumped to 50 percent of the total in 1942. Comparison of the distribution for 1928 and 1941 shows long-term changes in composition of sales for peacetime building. Notable differences are the increased percentage represented




FIGURE 2.—Percentage distribution of total sales value, f. o. b. plant, of gypsum products in 1928, 1941, and 1942, by groups of products.

by value of lath and the decline in importance of the building-plaster

group.

As a result of record consumption of portland-cement retarder and agricultural gypsum, total sales of uncalcined products advanced 15 percent over the tonnages sold in 1941. Unprecedented activity in the portland-cement industry raised indicated consumption of gypsum as retarder 8 percent over the record of 1941. Sales of agricultural gypsum increased 69 percent over the 1941 tonnage, a gain due to increased use in both major consuming areas—California and the Virginia-Carolina peanut section. In California, where "land plaster" is used on a large variety of crops to correct sulfate deficiency and to remedy black-alkali soils, consumption 2 has increased phenomenally, from 7,914 tons in 1934 to about 186,000 tons in 1942. In the Virginia-North Carolina area sales totaled approximately 60,000 tons, a 20percent increase over 1941. A study 3 of markets for agricultural gypsum indicated possible expansion in the "southeast" and "southwest" peanut-growing sections of the country.

<sup>&</sup>lt;sup>2</sup> California Department of Agriculture, Bureau of Chemistry, Commercial Fertilizers—Agricultural Minerals: Spec. Pub. 188, 1941. p. 94.

<sup>3</sup> Moyer, Forrest T., Expanding Markets for Agricultural Gypsum: Am. Fertilizer, vol. 97, No. 9, October 24, 1942, pp. 5–6.

The aggregate tonnage of industrial plasters sold in 1942 declined 6 percent from 1941 because of the 62-percent slump in the plate-glass and terra-cotta group which was only partly compensated by sharply increased sales of all other types of industrial plasters. The decline in consumption of plate-glass and terra-cotta plasters resulted from the closing of the principal consuming market—polished plate glass for passenger automobiles.

Gypsum products (made from domestic, imported, and byproduct crude gypsum) sold or used in the United States, 1941-42, by uses

		1941			1942			
Use	Short	Val	ue	Short	Val	118		ent of ge in—
	tons	Total	Aver- age	tons	Total	Aver-	Ton- nage	Aver- age value
Uncalcined:								
Portland-cement retarder Agricultural gypsum Other uses 1	149, 196 18, 074	667, 342 1 166, 706	4. 47 9. 22	251, 998 17, 638	166, 690	3. 27 9. 45	+69 -2	-27
Total uncalcined uses	1, 320, 713	3, 138, 958		1, 514, 913	3, 533, 607		+15	
Industrial: Plate-glass and terra-cotta plasters Pottery plasters Orthopedic and dental plasters Other industrial uses 2	48, 214 26, 022	331, 860 338, 708 394, 661	6. 88 13. 02 34. 12	18, 096 30, 856 14, 319	119, 849 423, 927 438, 375	6. 62 13. 74 30. 61	-62 +19 +24	-4 - +6 -10
Total industrial uses					1, 840, 927			—13 ———
Building: Cementitious: Plasters:	-			112,700	1, 010, 921		-0	
Base-coat	1, 532, 829 132, 628 20, 878	13, 505, 974 774, 465 126, 391	8, 81 5, 84 6, 05	848, 280 101, 497 17, 527	7, 596, 058 638, 388 111, 348	6. 29	-45 -23	+2 +8
To mixing plants Gauging and molding Prepared finishes Insulating and roof-deck Other 3	171, 954 12, 882 24, 079	2, 125, 926 334, 040 200, 912	12, 36 25, 93 8, 34	105, 728 8, 990 48, 266	1, 279, 506 348, 818 385, 102	6. 35 12. 10 38. 80 7. 98	-16 -39 -30 +100	$^{+5}_{-2}$ $^{+50}$
Other 3_ Keene's cement_	14, 031 29, 816	520, 755 464, 219	37. 11 15. 57	12, 107 14, 848	485, 980 238, 467	40. 14 16. 06	-14 -50	-4 +8 +3
Total cementitious	1, 939, 097	18, 052, 682		1, 157, 243	11, 083, 667		-40	
Prefabricated.								
Lath 4  Wallboard 7  Sheathing board 8  Laminated board 9  Tile 18	1, 357, 641 612, 203 179, 275	23, 524, 812 16, 578, 698 3, 287, 699	\$ 12.76 \$ 21.88 \$ 18.73	873, 302 3 374, 550	12, 116, 144 23, 200, 410 7, 016, 015	\$ 22. 18 \$ 19.00	+38	8 −1 8 +1 8 +1
	190, 010	0, 290, 200	11 39. 53	55, 676 143, 221	1, 464, 090 2, 915, 884	27, 54 1 45, 81	6 - 29	
Total prefabricated	2, 347, 697	46, 681, 489		2, 164, 387	16, 712, 543		-8	
Total building uses		64, 734, 171			7, 796, 210			
Frand total value		69, 758, 442			3, 170, 744	-		

<sup>1</sup> Includes uncalcined gypsum sold for use as filler and rock dust, in paint manufacturing, and for minor

purposes.

Includes statuary, industrial casting and molding plasters, dead-burned filler, and miscellaneous sales.
Includes joint filler, patching and painter's plaster, and unclassified building plasters.
Includes joint filler, patching and painter's plaster, and unclassified building plasters.
Includes joint filler, patching and painter's plaster, and unclassified building plasters.
Includes part M square feet, 1942: 959,307 M square feet.
Percent of change in square footage.
Includes partition, roof, floor, soffit, shoe, and all other gypsum tiles and planks—1941: 34,877 M square feet; 1942: 24,664 M square feet.
Includes partition, roof, floor, soffit, shoe, and all other gypsum tiles and planks—1941: 34,877 M square feet; 1942: 24,664 M square feet.
In Average value per M square feet of partition tile only.

In the cementitious group of building products only the insulating and roof-deck plasters showed increased sales over 1941; volumes of all other items declined sharply. Although sales of lath and tiles in the prefabricated group of products were markedly lower than in 1941, the loss was fully compensated by the record volumes of wallboard, sheathing, and laminated board sold. The decline in consumption of tiles was due to a decrease of nearly one-half in the square footage of




FIGURE 3.—Trends in sales of lath and base-coat plasters, 1938-42, by quarters.

partition tile sold and of approximately one-tenth in sales of all other

tile shapes (roof, floor, soffit, plank, etc.).

The sharp change in trends of sales of lath and base-coat plasters early in 1942 is shown in figure 3, which was compiled from data in Bureau of Mines Quarterly Gypsum Reports. The annual volume of lath sold has increased each year since 1933 and after 1935 set new records each year through 1941. After a slight recession in 1938 sales of base-coat plasters also increased through 1941. The change in types of materials required for wartime from peacetime building resulted in a marked decline in demand early in 1942 for these "built-in" products, and sales fell rapidly to a fourth-quarter volume that was well below similar data for any of the years shown.

Gypsum board and tile sold or used in the United States, 1928-42, by types

		Lath		Wallboard 1					
Year	M square feet	Value	•		Valu	в			
	M square leet	Total	Average 2	M square feet	Total	Average 2			
1928 1929 1930 1931 1932 1933 1934 1936 1936 1937 1938 1939 1940 1941 1941	405, 500 412, 000 341, 000 226, 500 117, 000 127, 000 252, 000 479, 000 738, 929 809, 471 1, 137, 415 1, 450, 669 1, 843, 648 959, 307	\$5, 775, 000 5, 475, 000 5, 625, 000 3, 425, 000 2, 100, 000 1, 675, 000 1, 680, 000 7, 325, 000 7, 325, 000 9, 604, 372 10, 287, 935 14, 598, 868 18, 189, 358 23, 524, 812 12, 116, 144	\$14. 24 13. 29 16. 50 15. 12 16. 41 14. 32 14. 57 15. 08 15. 29 13. 00 12. 71 12. 84 12. 54 12. 63	1 605, 500 1 667, 000 1 449, 500 1 366, 500 1 211, 000 1 203, 000 1 212, 000 1 244, 500 1 385, 307 1 371, 767 405, 655 491, 291 757, 588 1, 046, 025	1 \$11, 475, 000 1 12, 275, 000 1 11, 350, 000 1 19, 450, 000 1 5, 425, 000 1 5, 675, 000 1 6, 875, 000 1 8, 250, 000 1 8, 250, 000 1 8, 250, 000 1 8, 349, 810 1 7, 921, 400 8, 766, 184 10, 595, 245 16, 578, 698 23, 200, 410	1 \$18. 95 1 18. 44 1 25. 22 1 25. 75 1 28. 06 1 26. 77 1 26. 44 1 23. 95 1 21. 67 21. 61 21. 57 21. 88 22. 18			

		Sheathing 1		La	minated boa	rd 3	Tile 4				
Year	M Value		le	м	Valu	le	M	Valu	Value		
	square feet	Total	Aver- age 2	square feet	Total	Aver- age 2	square feet	Total	Aver- age <sup>5</sup>		
1928 1929 1930 1931 1932 1932 1933 1934 1935 1936 1937 1938 1939 1940 1941 1941	5, 221 89, 631 175, 496 369, 313	\$105, 649 1, 632, 688 3, 287, 699 7, 016, 015	\$20. 24 18. 22 18. 73 19. 00	6 53, 170	\$1, 464, 090	\$27. 54	50, 500 54, 600 40, 800 27, 300 10, 100 9, 800 12, 200 22, 300 22, 3820 19, 942 30, 191 30, 026 34, 877 24, 664	\$2, 400, 000 2, 400, 000 1, 780, 000 1, 160, 000 550, 000 740, 000 1, 380, 000 1, 552, 248 1, 300, 830 2, 066, 086 1, 962, 963 3, 290, 280 2, 915, 884	\$42. 99 37. 74 36. 88 37. 74 40. 79 38. 23 42. 84 42. 38 43. 19 42. 04 42. 45 43. 87 45. 58 39. 53 45. 81		

<sup>1</sup> Reportedly negligible square footages and values of sheathing are included under "Wallboard," 1928-38, inclusive

In the accompanying table listing annual data of the prefabricated gypsum products, average unit values are presented for the first time. Notable features of the series, not mentioned elsewhere in this chapter, are the over-all declines in average unit value of lath from 1930 to 1942 and in unit value of wallboard from 1932 to 1938, followed by a slight increase to 1942. Average values of wallboard vary more than those for lath because of annual fluctuations in demand for wallboard of different thickness and finish. The annual average values of partition tile likewise vary owing to changes in demand for the different thicknesses available. In studying price trends of gypsum products, it should be remembered that the industry experienced a disastrous price war in 1928-29.

ictusive.

2 Per M square feet, f. o. b. producing plant.

3 New product first marketed in 1942.

4 Includes partition, roof, floor, soffit, shoe, and all other gypsum tiles and planks.

5 Per M square feet, f. o. b. producing plant, of partition tile only.

6 Reported as area of component board and not of finished product.

#### **PRICES**

Prices of gypsum products as indicated by reported mill values showed a slight upward tendency in 1942, although no significant changes. Average mill values per unit have been remarkably stable in recent years. The decline from 1941 in average value of agricultural gypsum was caused by the increased tonnage of low-priced gypsite sold for such use in California. In 1942 the average mill value was \$1.91 per ton for agricultural gypsum in California compared with \$6.03 per ton for land plaster in the Virginia-North Carolina area where rock gypsum is used exclusively.

A study 4 of wholesale and retail prices of building materials states that gypsum plasters generally are marketed under a freight equalization system. The average wholesale and retail prices of plaster in September 1939 in the 50 cities surveyed were \$13.58 and \$17.57 per ton, respectively, a spread of 29.4 percent. Wholesale prices showed a fairly large geographical variation and were lowest in the

Middle Atlantic and highest in the East South Central States.

## RECENT DEVELOPMENTS

The most notable achievement in 1942 was the development of laminated gypsum-board products which are available at the mill with a wide variety of surfacing materials ranging from those suitable for exposure to weather to those for finished interiors without further decoration. The products are made in thicknesses up to 2 inches and are composed of two, three, or four plies of gypsum boards.

Use of gypsum plaster to make molds and cores for nonferrous metal casting is developing rapidly. A description of the patented Capaco process, which utilizes a mixture of 79 percent calcined gypsum, 20 percent fibrous magnesium silicate, and 1 percent set accelerator, claims marked advantages for gypsum over sand molds. This process already is used in four casting plants, one of which has a daily capacity of 20,000 pounds of nonferrous metals.

In England patterns of gypsum plaster are used more widely than in former years as a means of speeding foundry work. Recent developments in production technique and the advantages of plaster

patterns in foundry work have been described.6

Press tools of gypsum plaster made by direct molding have been investigated in England for small-quantity production of metal pressings.

A new industrial use for gypsum is the forming of self-sealing liners

for bulletproof gasoline tanks over molds of plaster.

Experience 8 has shown that the properties of a high-strength gypsum cement developed recently make it a satisfactory material for certain uses in cementing and shooting oil wells.

Preliminary work 9 on fusion of a mixture of salt, silica, and gypsum produced a glass free of bubbles and specks. Advantages of the

<sup>4</sup> Temporary National Economic Committee, Geographical Differentials in Prices of Building Materials; Mon. 33, 1940, pp. 47-63.

4 Phair, W. A., Plaster Molds: Iron Age, vol. 148, No. 15, October 9, 1941, pp. 74-78.

5 Phair, W. A., Plaster Patterns: Aircraft Production, vol. 4, No. 37, November 1941, pp. 13-16; Plaster Patterns for Foundry Use: Foundry Trade Jour., vol. 66, January 15, 1942, pp. 35-36.

7 Plucknett, Henry, Molded Press Tools: Aircraft Production, vol. 4, No. 39, January 1942, pp. 139,

8 Henderson, R. K., New Fast-Setting Cement is Valuable Odd-Job Adjunct: Petrol. Eng., vol. 11, No. 13, 1940, pp. 33-34.

9 Dertev, N. K., Glass, Sulfuric Acid, and Hydrochloric Acid From Sodium Chloride, Silica, and Gypsum: Jour. App. Chem. (U. 8. 8, R.), vol. 14, 1941, pp. 703-705.

process are the volatilization of one-fourth of the iron content in the charge, which permits the use of low-grade silica, and the possible

recovery of sulfuric and hydrochloric acids as byproducts.

In the late 1930's, practice at the New Caledonia nickel smelter was changed by substitution of gypsum for sulfur in the process as an economic measure. Approximately 6 tons of gypsum does the work of 1 ton of sulfur. At capacity operation monthly requirements <sup>10</sup> of gypsum by the smelter are 2,500 short tons, of which nearly all is obtained from local sources.

#### FOREIGN TRADE 11

Nearly all the foreign trade of the United States in gypsum consists of crude gypsum imported from Nova Scotia and New Brunswick, Canada, to processing plants along the east coast as far south as Florida. Developments in 1942 in the flow of crude supplies are dis-

cussed earlier in this chapter.

Imports and exports of gypsum products are negligible in quantity and value in contrast with the volume of domestic business. Imports in the classes "Alabaster manufactures" and "Other manufactures" have declined sharply in recent years; they virtually ceased in 1942 because of the stoppage of trade with Italy, the principal source. In export trade the only significant change from 1941 was the trebling in square footage of exports of gypsum board owing doubtless to offshore construction activities of the Federal Government and to demand for board to repair bombed buildings in England.

Gypsum and gypsum products imported for consumption in the United States, 1938-42

Year	Crude (including anhydrite)		Ground		Calcined		Keene's cement		Ala- baster manu-	Other manu-	Total
Year	Short tons	Value	Short tons	Value	Short	Value	Short tons	Value	fac- tures 1	fac- tures, n. e. s.	value
1938	1, 405, 210	1, 174, 117 1, 300, 450 1, 225, 152	1, 475 1, 137 1, 631	\$17, 674 17, 606 16, 206 30, 499 20, 427	372 302 223 242 309	5, 087 6, 416	4 9 34	145 265 945	71, 143 3, 232	55, 412 36, 138 15, 896	1, 429, 289 1, 282, 140

<sup>&</sup>lt;sup>1</sup> Includes imports of jet manufactures, which are reported to be negligible.

Crude gypsum (including anhydrite) imported for consumption in the United States, 1940-42, by countries

Country	19	40	19	41	19	42	
Country	Short tons	Value	Short tons	Value	Short tons	Value	
CanadaChina	1, 368, 194	\$1, 260, 076	1, 345, 681	\$1, 220, 761 88	397, 511	\$476, 900	
Dominican Republic Hong Kong			6	240	3, 053	9, 076	
Italy Mexico	184	4, 495					
United Kingdom 1	32, 134 4, 698	29, 056 6, 823	2, 268	4, 063	952	918	
	1, 405, 210	1, 300, 450	1, 347, 957	1, 225, 152	401, 516	486, 894	

<sup>&</sup>lt;sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

<sup>&</sup>lt;sup>10</sup> Bureau of Mines, Mineral Trade Notes: Confidential Ser., No. 10, April 1943, pp. 23-24.
<sup>11</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

GYPSUM Gypsum and gypsum products exported from the United States, 1938-42

	Crude, or gr	crushed, ound	Plasterbo wallb		Calc	ined	Other manu-	Total	
1 ear	Year Short tons Valu		Square feet	Value	Short tons Value		factures, n. e. s.	value	
1938 1939 1940 1941 1942	2, 844 10, 342 5, 209 15, 491 595	\$17, 762 41, 012 31, 564 72, 877 14, 543	3, 658, 647 5, 258, 249 4, 152, 452 13, 560, 482 39, 489, 186	\$88, 822 130, 073 101, 680 296, 848 772, 989	3, 833 2, 913 2, 208 3, 041 1, 859	\$71, 914 69, 577 56, 419 90, 397 84, 784	\$104, 284 68, 791 74, 465 69, 452 105, 547	\$282, 782 309, 453 264, 128 529, 574 977, 863	

### WORLD PRODUCTION

World production of gypsum in 1942, based upon the meager data available, is estimated at approximately 9½ million metric tons.

Since the outbreak of war in 1939, output of gypsum in nearly all European countries that are large producers—France, United Kingdom, Russia, and Germany—undoubtedly has slumped because of the stoppage of residential building. The industries of those countries, unlike the United States, have not developed the manufacture of gypsum boards for which demand in 1942 has been so large in this country as to cushion the decline in plaster consumption. In European countries demand for gypsum as cement retarder probably is greater because of the increased activities of the portland-cement industries to fill needs for fortifications and other military purposes and for industrial and bombproof construction. Compensating in part for the decline due to cessation of building, consumption of gypsum and anhydrite as raw materials for the manufacture of sulfuric acid and sulfide and sulfate chemicals doubtless has gained appreciably in the past few years because of difficulties in obtaining supplies of sulfur and pyrite. After the World War of 1914-18 the processes utilizing gypsum and anhydrite were developed to economic feasibility in the laboratory, and commercial plants 12 employing them were in operation in the United Kingdom, France, and Germany at the outbreak of the present war.

In Spain, the only other European country with sizable production, output of gypsum probably has increased in recent years because of the necessary rehabilitation of buildings destroyed during the Civil War of 1936–39.

Activity of the gypsum industry in Canada during 1942, in terms of crude output, was only about one-third that in 1941. The decline was caused by the severe curtailment of crude exports to the United States and the halting by the Dominion Government of all building not essential to the war effort.

<sup>&</sup>lt;sup>13</sup> Bureau of Mines Minerals Yearbook, 1938, p. 1091; 1940, p. 1235.

World production of gypsum, 1937-42, by countries, in metric tons 1 [Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
Algeria	46, 175	33, 325	(2)	(2) (2)	(2)	(2)
Anglo-Egyptian Sudan				(2)	(2)	(2)
Argentina 3	68, 220	70, 813	87, 328	103, 157	86,076	(2)
Australia:	1		,			``
New South Wales	9, 300	12,712	(2)	(2)	(2)	(2)
South Australia		148, 943	147, 266	155, 901	115, 323	(2)
Victoria	21, 197	13, 596	11, 966	(2)	(2)	(2)
Western Australia		13, 645	14, 570	13,020	(2)	(2)
Belgian Congo		1,000	(2)	500	(2)	(z)
Brazil 4	2,000	2,000	2,000	2,000	(2)	25
Canada		915, 169	1, 289, 950	1.314.311	1, 445, 506	526, 686
Chile		24, 551	22, 209	25, 865	23, 125	
China:		(2)	(2)	75,000	(2), 120	(2) (2)
Cuba		7, 257	6, 270	12,000	12,000	<u> </u>
Cyprus		5 9, 729	5 5. 058	4 1, 400	(2)	<u> </u>
Egypt		212. 088	700, 166	169, 723	130, 942	$\sim$
Eire		13, 364	16, 168	21, 662	24, 660	(2) (2) (2) (2)
		13, 915	(2)	(2)	(2)	(2)
Estonia	1 200 400	19, 919	(2)	(2)		
France		(2) (2)	(2)	(2)	(2) (2) (2) (2) (2)	(2) (2) (2) (2) (2)
Germany	(2)		(2)	(2)	(2)	(2)
Austria 6	47, 000	(2) 16, 609		(2) (2)	(2)	
Greece	17, 924		15, 219	(2)	(2)	(2)
India, British		70, 944	69, 786	(2)		
[raq			69, 545	34, 879	(2)	(2)
[taly		425, 299	(2)	(2) (2)	(2)	(2)
Latvia		220,000	245, 035	(2)	(2) (2) (2) (2)	(2) (2) (2) (2)
Luxemburg	19, 722	19, 901	(2)	(2)	(2)	(2)
New Caledonia	984	1,070	(2)	3,000	(2)	(2) (2) (2)
Palestine		3, 984	4, 524	4, 403	(²) 25, 000	(3)
Peru	12, 895	14,026	15, 655	21, 478	25,000	(2)
Portugal Rumania	11, 390	9, 036	(2)	(2)	(2)	(2) (2)
		69, 079	(2)	(2)	(2)	(2)
Sweden	108	95	102	(2)	(2)	(2)
Switzerland		35,000	38,000	30,000	(2)	(2)
Funisia	22, 800	(2)	(2)	(2)	(2)	- (2)
Union of South Africa	33, 186	38, 849	40, 782	(2)	(2)	(2)
United Kingdom	1, 111, 669	1, 109, 928	(2)	(2)	(2)	(2)
United States	2, 774, 307	2, 435, 057	2, 927, 231	3, 355, 672	4, 344, 062	4, 261, 540

<sup>In addition to the countries listed gypsum is produced in Chosen, Japan, French Morocco, Mexico, Poland, Spain, U. S. S. R., and Yugoslavia, but production data are not available.
Data not available.
Approximate production.
Approximate production.
Exports of crude and calcined gypsum.
Estimate furnished by Bundesministerium für Handel und Verkehr.</sup> 

# LIME

#### By Forrest T. Moyer and F. D. Gradijan

#### SUMMARY OUTLINE

	Page		Page
Summary	1297	Trends in principal uses	1305
Salient statistics	1298		1308
Production	1300	Total shipments	1308
Captive tonnage	1301	Hydrated lime	1308
Production by States	1302		1311
Production by uses	1302	New developments	1311
Lime and other liming materials used in		Plant capacity	1311
agriculture	1302		
Building lime	1305	Foreign trade	1313
Chemical and industrial lime	1305	Imports	1313
Hydrated lime	1305		1313
Troop	1205		

#### SUMMARY

The net effect of the change from peacetime to wartime economy in 1942 benefited the lime industry, and total sales of "open-market" lime advanced slightly over 1941 to a new record of 6,103,791 short tons. However, not all branches of the industry shared in the increased business. Sales of agricultural, chemical, and refractory (dead-burned dolomite) lime were well above the volumes sold in 1941, but sales of building lime slumped sharply from the 1941 tonnage. The first year of war also effected a marked change in demand for the two types of lime, as shown by the 7-percent gain in total quantity of quicklime sold and the 19-percent decrease in sales of hydrated lime from 1941. Although labor, fuel, and material costs rose sharply in 1942, prices of lime increased only slightly and remained in the narrow range of fluctuation that has prevailed for the past 10 years. The average value, f. o. b. plant, advanced 21 cents over 1941 to \$7.27 per ton.

Although increases in hourly rates of pay were reported by producers in nearly all States, a serious labor shortage prevailed throughout the lime industry during 1942. Also, a high turn-over rate left many plants with an inefficient labor force. These factors increased production costs markedly, as operators were forced to pay overtime rates to meet the demand for lime. As selling prices showed little change from 1941, the increased costs and the short labor supply compelled many plants (mostly small producers) to close during 1942.

Other than price freezing, no direct war controls were imposed on the lime industry during 1942. The General Maximum Price Regulation of the Office of Price Administration, effective May 11, froze all lime prices at the highest selling value, f. o. b. plant, obtained during March 1942. Effective August 1, Maximum Price Regulation 188 of the same agency removed lime from the general order and continued the March prices as maximum. The stoppage of nonessen-

tial public and private construction by War Production Board Conservation Order L-41 of April 9 and its more restrictive revision of September 7 had direct adverse effect on sales of building lime.

The demand for chemical lime increased steadily throughout 1942 in nearly all sections of the country, and total sales for this classification advanced 6 percent over the former record tonnage sold during At the year's end, shortages had developed in several localities in which war plants with large lime requirements had been built or expanded, and supplies had to be brought in from relatively distant lime plants. Consumption of chemical lime by the various industries showed diverse effects of the war, and the quantities sold for many of the chemical uses declined in 1942 from 1941. However, most of the decreased requirements were in industries with relatively small consumption, whereas nearly all the large consuming industries, notably metallurgical, carbide, glass, and water-purification, purchased more lime in 1942.

Salient statistics of the lime industry in the United States, 1925-29 (average), 1935-39 (average), and 1940-42

	1925-29 (average)	1935–39 (average)	1940	1941	1942
Active plants	419	310	314	309	270
Sold or used by producers: By types:					
Quicklimeshort tons_ Hydrateddo	2, 871, 236 1, 585, 631				
Total lime: Short tons. Value <sup>1</sup> Per ton	4, 456, 867 \$38, 548, 498 \$8. 65	\$26, 592, 115	\$33, 956, 385	6, C79, 416 \$42, 941, 162 \$7. 06	\$44, 367, 441
By uses: Agricultural short tons Building do Chemical and industrial do Refractory (dead-burned dolomite) do	318, 224 2, 096, 744 1, 623, 885 418, 014	870, 335 1, 929, 947	1, 010, 435 2, 643, 762	1, 065, 599 3, 561, 203	697, 677
Imported for consumption: Short tons	18, 683 \$344, 887				
Short tonsValue	15, 752 \$221, 177		31, 912 \$311, 619		(3)

Selling value, f. o. b. plant, excluding cost of containers.
 Figures cover January-September, inclusive.
 Data not available.

The high rate of operations and the installation of new open-hearth and electric-furnace capacities in the steel industry, the coming into production of new or expanded magnesium and Bayer alumina plants, and the increased quantities of metallic ores floated during 1942 raised the total demand for metallurgical lime 15 percent above 1941. The only reduced market for metallurgical purposes was for cyanida-The demand for lime in the Bayer alumina process tion of gold ores. doubtless will increase, because lime requirements per ton of ore rise rapidly as lower-grade bauxites are used. Owing to greatly increased requirements for acetylene in welding and synthetic rubber, consumption of lime for carbide manufacture advanced 49 percent over 1941. Demand for lime in glass manufacture and water purification also increased in 1942. The only chemical uses that annually consume large quantities of lime to show decreased consumption from 1941 were in the insecticide and disinfectant, paper, and tanning industries.

LIME 1299

Sales of refractory lime reached a new high volume in 1942 and surpassed the 1941 tonnage by 15 percent—a greater proportional gain than was shown by output of steel. This increased demand resulted in part from the quantities needed for bottoms in new open-hearth furnaces and indicates continued substitution of dead-burned and stabilized dolomites for other higher-priced or less available refractories as well as wider acceptance of the enriched dolomitic-base materials.

War controls on the construction industry and the changes in types of materials required in wartime compared with peacetime building resulted in a sharp decline in total sales of building lime from 1941. As speed of erection was the first requisite of all wartime construction, the automatically reduced volume of masonry work caused a slump in consumption of lime for masonry purposes. Also, the demand for finishing lime declined markedly from 1941, because most of the war and military housing in 1942 consisted of small, low-cost units designed for the use of prefabricated rather than "built-in" materials.

Despite record farm income in 1942 and growing recognition of the importance of calcium as a plant food, consumption of agricultural lime increased only 5 percent over 1941. This increase compares unfavorably with the 38-percent gain in cash farm income

from crops and Government subsidies in 1942 over 1941.

A notable feature of figure 1, which shows trends in major uses of lime from 1922 to 1942, is the rapid rate of recovery in sales of chemical and refractory lime from the low volumes of 1932. Consumption in these uses after 1935 set new annual records in each year through 1942, except in 1938, when sales declined. The building-lime curve




FIGURE 1.—Trends in major uses of lime, 1922-42.

shows the longest decline, extending from 1925 through 1934, with only partial recovery since that time. The demand for agricultural lime is more stable than for other uses, and annual sales show comparatively small fluctuations as well as the lowest rates of gain or loss. In contrast, sales of refractory lime have the greatest proportional fluctuation and also the most rapid rates of increase or decrease, as shown by the slope of the curve from year to year.

## PRODUCTION

As quicklime is a semiperishable commodity and most plants have only small storage facilities, stocks of lime in the hands of producers are never large. Hence, in this chapter, the tonnages of "openmarket" lime sold or used are considered equivalent to production

and are used interchangeably.

Production of all classes of lime, by major uses, increased over 1941 except building lime, for which a decline of 35 percent was recorded. The largest proportional gain was shown in the output of refractory lime (dead-burned dolomite). It is noteworthy that the production of hydrated lime declined in all of the major use categories and that the decline in total output of this type from 1941 was 19 percent. The production of quicklime increased in all principal uses except for building purposes, for which output slumped 38 percent below 1941.

Lime sold or used by producers in the United States, 1941-42, by types and major uses

		. 1	941				1942			
	Quan	Quantity		Value 1		Quantity		1		ent of ge in—
	Short tons	Per- cent of total		Av- er- age	Short tons	Per- cent of total		Av- er- age	Ton- nage	Av- erage value
By types: Quicklime Hydrated lime	4, 489, 257 1, 590, 159	74 26	\$30, 586, 364 12, 354, 798	\$6. 81 7. 77	4, 810, 452 1, 293, 339	79 21	\$34, 077, 137 10, 290, 304	\$7.08 7.96		+4 +2
Total lime 2	6, 079, 416	100	42, 941, 162	7.06	6, 103, 791	100	44, 367, 441	7. 27		+3
By uses: Agricultural: Quicklime Hydrated lime	161, 063 221, 664					3 4	950, 374 1, 568, 579	5. 15 7. 26	+15 -3	-4 +6
	382, 727	6	2, 387, 045	6. 24	400, 631	7	2, 518, 953	6. 29	+5	+1
Building: Quicklime Hydrated lime	285, 271 780, 328	13		9. 09 8. 54		3 8	1, 644, 316 4, 528, 889	9. 36 8. 68	-38 -33	+3 +2
	1, 065, 599	17	9, 259, 118	8. 69	697, 677	11	6, 173, 205	8. 85	-35	+2
Chemical and industrial: Quicklime Hydrated lime	2, 973, 036 588, 167	49 10	18, 014, 672 4, 169, 155		3, 220, 774 555, 352	53 9	20, 664, 813 4, 192, 836	6. 42 7. 55	+8 -6	+6 +6
	3, 561, 203	59	22, 183, 827	6. 23	3, 776, 126	62	24, 857, 649	6. 58	+6	+6
Refractory (dead-burned dolomite)	1, 069, 887	18	9, 111, 172	8. 52	1, 229, 357	20	10, 817, 634	8. 80	+15	+3

Selling value, f. o. b. plant, excluding cost of containers.
 Includes lime used by producers (captive tonnage) as follows—1941: 499,062 short tons valued at \$2,556,-240; 1942: 427,635 tons, \$2,239,162.

Lime sold or used by producers in the United States, 1941-42, by States

		1941			1942	
State	Active plants	Short tons	Value	Active plants	Short tons	Value
Alabama	9	306, 836	\$1, 705, 558	9	330, 552	\$1,916,985
Arizona	3	58, 146	413, 095	4	59, 033	439, 817
Arkansas	2	(1)	(1)	2 9	(1)	(1)
California	9	122, 375	1, 168, 767	3	83, 399	905, 923
Colorado	3	(1)	$\mathbb{R}^{2}$	1	(1)	$\aleph$
Connecticut	1 4		216, 254	4	21, 510	212, 291
Florida	1	23, 265 12, 515	85, 325	1	10, 824	68, 323
Georgia	1	8, 681	137, 195	1	8, 863	140, 762
Hawaii	i	120	2, 160	-	0,000	110, 102
Idaho	9	246, 574	1, 702, 129	9	314, 078	2, 269, 743
IllinoisIndiana	3	106, 407	588, 879	3	102, 757	608, 656
Louisiana	2	(1)	(1)	ĭ	(1)	(1)
Maire	2	(1)	M	2	) is	<u>```</u>
Maryland	13	65, 624	431, 200	11	62, 871	371, 189
Massachusetts	6	106, 336	1, 007, 773	6	87, 537	757, 109
Michigan	4	55, 447	388, 104	5	58, 283	420, 523
Minnesota	2	(1)	(1)	2	(1)	(1)
Missouri	11	736, 200	4, 106, 468	10	853, 020	4, 915, 784
Montana	2		(1)	2	(1)	(1)
Nevada	3	(1)	(1)	2	(1)	(1)
New Jersey	4	(1)	(1)	3	(1)	(1)
New Mexico	2	(1)	(1)	. 1	(1)	(1)
New York	5	62, 339	463, 230	4	68, 443	552, 411
North Carolina	1	(1)	(1)	1	(1)	(1)
Ohio	22	1, 549, 246	12, 482, 106	23	1, 418, 161	11, 739, 547
Oklahoma	3	(1)	(1)	3	(1)	(1)
Oregon	1	3,940	21, 524	1	(1)	(1)
Pennsylvania	89	1, 003, 039	7, 263, 779	62	1, 030, 156	7, 703, 095
Puerto Rico	6	8, 159	114, 728	7	10, 178	162, 796
Rhode Island	1	(1)	(1)	1	(1)	(1)
South Dakota	2	(1)	(1)	2	(1)	(1)
Tennessee	10	239, 528	1, 354, 642	10	269, 566	1, 620, 585 559, 279
Texas	9	77, 783	632, 099	8	67, 377	392, 912
Utah	9	56, 221	352, 306	6 5	57, 609	462, 908
Vermont	5	67,824	479, 219	25	71, 642 206, 420	1. 367, 043
Virginia	25 4	224, 293 62, 309	1, 359, 281 656, 363	3	55, 864	623, 766
Washington	10	372, 677	2, 350, 362	8	422, 481	2, 879, 509
West Virginia	10	79,077	659, 324	10	63, 801	499, 279
Wisconsin Undistributed 2	10	424, 455	2, 799, 292	10	369, 366	2, 772, 206
Oligishi ibarea		121, 100	4, 190, 494		500, 500	2, 2, 200
	309	6, 079, 416	42, 941, 162	270	6, 103, 791	44, 367, 441

1 Included under "Undistributed."

#### CAPTIVE TONNAGE

The lime industry, as defined by Bureau of Mines statistics, is limited as far as possible to operators who produce lime for sale to con-Captive tonnage of companies that produce lime for internal consumption is excluded with only a few exceptions. Hence the annual review figures are confined largely to "open-market" lime sold under competitive conditions. However, to obtain complete data on quantities of lime consumed for certain uses that are not covered by other Bureau of Mines statistics, it is necessary to include some captive tonnage. In 1942 the captive tonnage contained in the lime figures totaled 427,635 short tons valued at \$2,239,152. This total comprised 11,429 tons of lime for making prepared masonry mortars, 312,557 tons for metallurgical uses (of which approximately half was for steel manufacture and half for ore concentration), 16,864 tons for miscellaneous chemical uses, and 86,785 tons of refractory lime.

<sup>&</sup>lt;sup>1</sup> Included under "Undistributed."

<sup>2</sup> By groups of States as follows—1941: Maine, Rhode Island, Connecticut, and New Jersey, 79,962 short tons valued at \$639,559; North Carolina, Louisiana, Arkansas, and Oklahoma, 189,058 tons, \$1,086,601; Minnesota and South Dakota, 63,655 tons, \$486,436; Colorado, New Mexico, Montana, and Nevada, 91,780 tons, \$586,696. 1942: Maine, Rhode Island, Connecticut, and New Jersey, 77,039 tons, \$601,068; North Carolina, Louisiana, Arkansas, and Oklahoma, 102,282 tons, \$302,873; Minnesota and South Dakota, 64,963 tons, \$495,562; Colorado, New Mexico, Montana, Nevada, and Oregon, 125,082 tons, \$872,703.

approximate total consumption of lime in alkali, carbide, glass, magnesia (85 percent), paper, and sugar manufacture may be ascertained by combining the "open-market" lime figures for these uses with the statistics (after allowances for calcining loss) on similar uses for limestone in the Stone chapter of Minerals Yearbook. The figures in the Stone chapter include limestone used to make captive lime but exclude the stone used to produce "open-market" lime.

#### PRODUCTION BY STATES

The first year of war effected sharp changes in the location of production of lime from 1941. The record output of 1942 was obtained from 270 plants in 37 States and 2 Territories; production increased in 16 States and 2 Territories and declined in 21 States from 1941. No production was reported for Idaho in 1942. The ranking producing States, in order of tonnage, were Ohio, Pennsylvania, Missouri, and West Virginia, which together supplied 61 percent of the total. Although the slump in building lime had a marked effect on production in Ohio, the strong demand for refractory and chemical lime offset the loss in part, and output declined only 8 percent from 1941. Production in the other 3 ranking States that are large producers of chemical lime was greater than in 1941.

In 1942 only 270 plants were active compared with 309 in 1941. Nearly all the plants forced to close by labor, price, or other reasons directly attributable to the war were small producers. The greatest number closed in Pennsylvania, in which 27 plants ceased operating

either temporarily or permanently.

#### PRODUCTION BY USES

In 1942 the largest gains over 1941 in tonnages of lime consumed in the principal uses were recorded for metallurgical and refractory (dead-burned dolomite) purposes and for the manufacture of calcium carbide.

In this chapter, data on the production of lime for its many uses are presented in one table, whereas in former annual reviews the figures were listed in two tables, one for the major uses and a second for mis-

cellaneous uses of chemical and industrial lime.

Lime and other liming materials used in agriculture.—Although production of lime for agricultural purposes gained 5 percent over 1941, the increase was in much smaller proportion than that reported for cash farm income. The output in Pennsylvania, the State with the largest production for agriculture, declined 3 percent from 1941, owing doubtless to closing of a large number of the small plants because of labor shortages.

In the markets for liming materials, lime lost further ground to ground limestone or "agstone," production of which increased 15 percent over 1941. Of the other materials, the output in 1942 of crushed oyster shells declined slightly and that of marl increased

somewhat compared with 1941.

The state of the s

Lime sold or used by producers in the United States, 1941-42, by uses

		1941	1 1 1 1 1		1942	
Use	<b>61</b>	Valu	.е		Valu	е
	Short	Total	Average	Short tons	Total	Aver-
Agricultural	382, 727	\$2, 387, 045	\$6. 24	400, 631	\$2, 518, 953	\$6.29
Building: Finishing lime Mason's lime Prepared masonry mortars Unspecified	464, 564	4, 205, 669 3, 808, 074 416, 829 828, 546	9. 29 8. 20 6. 46 9. 87	281, 227 295, 037 51, 303 70, 110	2, 688, 734 2, 536, 952 362, 745 584, 774	9.56 8.60 7.07 8.34
	1, 065, 599	9, 259, 118	8.69	697, 677	6, 173, 205.	8.85
Chemical and industrial: Acid neutralization. Alkalies (ammonium, potassium, and sodium	1, 739	14, 222	8.18	5, 181	30, 124	5. 81
compounds)  Asphalts and other bitumens. Bleach, liquid and powder <sup>2</sup> Brick, sand-lime and slag Brick, silica (refractory) Calcium carbide and cyanamide. Calcium carbonate, precipitated Chromates and bichromates Coke and gas (gas purification and plant by	24, 966 3 136, 238	(1) 23, 112 100, 579 156, 081 168, 819 2 705, 333 3 48, 071 108, 649	(1) 8.43 6.85 7.26 6.76 35.18 38.30 5.94	7, 336 706 13, 161 20, 550 17, 507 202, 518 (1) 20, 538	51, 198 5, 592 97, 810 166, 779 135, 537 1, 114, 447 (1) 130, 902	6. 98 7. 92 7. 43 8. 12 7. 74 5. 50 (1) 6. 37
products:	22, 011	139, 499	6.34	17, 629	112, 355	6.37
Creameries and dairies Gelatin Other 4 Glasswork Glue. Grease, lubricating Insecticides, fungicides, and disinfectants Magnesia (85 percent) Medicines and drugs	4, 846 887 184, 559 12, 005 4, 001 81, 955 51, 256 (¹)	19, 877 32, 718 7, 658 1, 253, 700 83, 580 34, 787 587, 567 373, 999	16. 97 6. 75 8. 63 6. 79 6. 96 8. 69 7. 17 7. 30	1,427 7,223 8,952 190,580 7,886 4,996 66,332 24,635 6,021	19, 721 56, 083 80, 852 1, 402, 674 52, 224 43, 309 507, 730 166, 663 35, 479	13. 82 7. 76 9. 03 7. 36 6. 62 8. 67 7. 65 6. 77 5. 89
Nonferrous smelter flux Steel (open-hearth and electric furnace flux) Ore concentration but the following smelter flux Wire drawing Other but following smelter flux Paints Paper mills 7 Petroleum refining Polishing compounds Rubber manufacture Salt refining Sewage and trade-wastes treatment Soap and fat Sugar refining Tanneries Textiles Tobacco Varnish Water purification Wood distillation Undistributed but smelter flux Unspecified	45, 51.3 677, 116 34, 696 3, 922 3, 058 1, 956 38, 256 (1) 23, 169 93, 157 1, 091 (1) 864 319, 244 2, 557 156, 119 204, 952	\$ 41, 114 6, 179, 270 \$1, 332, 808 54, 355 462, 633 258, 298 4, 234, 772 252, 010 97, 987 22, 346 12, 593 245, 115 (1) 248, 602 649, 002 8, 210 (1) 5, 888 2, 072, 807 24, 106 777, 442 1, 346, 218	38. 23 5. 578 7. 740 5. 68 6. 25 7. 26 7. 26 6. 41 (1) 10. 73 6. 81 9. 43 4. 98 6. 57	3, 956 1, 171, 082 318, 436 9, 065 74, 058 14, 281 606, 440 30, 944 4, 113 25, 758 4, 113 25, 758 77, 655 78, 746 6, 858 311 335, 877 2, 901 31, 709 401, 075	39, 842 7, 508, 445 1, 942, 098 70, 274 529, 664 107, 429 4, 049, 884 267, 120 20, 836 10, 049 25, 604 177, 651 34, 676 315, 127 549, 828 7, 352 38, 865 2, 327, 177 28, 622 221, 665 2, 373, 273	10. 07 6. 41 6. 10 7. 75 7. 15 7. 15 7. 28 8. 63 27. 49 7. 28 6. 90 5. 20 6. 98 8. 44 5. 67 8. 65 6. 93 7. 8. 65 6. 93 7. 99 5. 92
Refractory lime (dead-burned dolomite)		22, 183, 827 9, 111, 172	6, 23 8, 52	3, 776, 126 1, 229, 357	24, 857, 649 10, 817, 634	6, 58 8, 80
Total lime • Hydrated lime included in above distribution	6, 079, 416 1, 590, 159	42, 941, 162 12, 354, 798	7.06 7.77	6, 103, 791 1, 293, 339	44, 367, 441 10, 290, 304	7. 27 7. 96

<sup>1</sup> Included under "Undistributed."

2 Excludes bleach used in paper mills.
3 Excludes bleach used in paper mills.
4 Revised figures.
4 Includes chocolate, cocoa, fruit juices, phosphate baking powders, and unspecified food products.
5 Includes flotation, cyanidation, bauxite purification, and magnesium manufacture.
6 Includes mold coating and unspecified.
7 Includes bleach used in paper mills.
8 Includes acids (unspecified), alcohol, bromine, calcium phosphate, cement manufacture, chloropicrin, explosives, glycerin, nicotine, photographic supplies, poultry feed, retarder, rock wool, Spanish whiting, starfish control, sulfur, and wool pullers.
9 Includes lime used by producers (captive tonnage) as follows—1941: 499,062 tons, valued at \$2,556,240; 1942: 427,635 tons, \$2,239,152.

# Lime sold or used by producers in the United States in 1942, by States and uses

State or Territory Sho ton		Value																
	ons		Short	Value	Metal	urgical	Pape	r mills	Tan	neries		purifi- tion	Ot	her	Short	Value	Short	Value
11-1			tons	value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	tons	value	tons	value
Alabama (1) Arizona (1) Arkansas	(1)	(1) (1)	41, 261 (1) (1)	\$273, 358 (1) (1)	175, 026 50, 965	\$940, 521 348, 618	82, 377	\$488, 388	(1)	(1)	6, 206	\$52, 469	(1) (1) (1)	(1) (1) (1)	(1)	(1)	330, 552 59, 033	\$1, 916, 985 439, 817
California (1)	526 (1) (1)	\$4,751 (1)	20, 467	249, 556		300, 212 (¹)	(1) (1) (1)	(1) (1)	(1)	(1)	5, 743	52, 027 (1)	23, 768 (¹)	\$267, 661	(1)	(1)	83, 399 (1)	905, <b>923</b>
Florida (1)	(1) 5, 864	(1) 19, 167	4, 713 6, 960 871	46, 734 49, 156 14, 888			(1)	(1)			7, 770	73, 998	8, 641 7, 992	88, 591 125, 874			21, 510 10, 824 8, 863	212, 291 68, 323 140, 762
Illinois (1) Indiana (1) Louisiana	439 (1)	2, 877 (1)	13, 032 6, 155	124, 521 42, 345 (1)	133, 190	799, 665 (¹)	12, 782	74, 353		\$82, 550	23, 894 14, 584	168, 934 89, 431	(1) 49, 016	(1)	(1)	(1)	314, 078 102, 757	2, 269, 743 608, 656
Maine (1) Maryland 52, 0 Massachusetts 7, 0	(1) 1, 012 1, 682	(1) 299, 484 54, 787	(1) (1) 29, 481 1, 023	(1) (1) <b>291,</b> 383	(1)	(1)	(1) (1) 9,878 (1)	(1) (1) 78, 781	(1) 9,670	73, 737	(1) (1) 4, 233 4, 868	(1) (1) 33, 447 37, 230	(1) (1) (1)	(1) (1) (1) 100, 196			(1) (1) 62, 871 87, 537 58, 283	(1) 371, 189 757, 109 420, 523
Minnesota (1) Missouri (1) Montana	(1)	(1)	(1) 41, 130	8, 263 (1) 273, 498 (1)	(1) 151, 139	(1) (1) 793, 904	(9)	(1)	(1) (1) (1)	(1)	(1) 89, 488	(1) 529, 257	13, 082 (1) 427, 139 (1)	2, 264, 495	(1)	(1)	08, 283 (1) 853, 020 (1)	(1)
New Jersey (1) New Mexico		(1) (1)	(1) (1) (1)	(1) (1) (1)	(1)	(1)					(1)	(1)	(1)	(1) (1)			(1) (1) (1)	(1) (1) (1)
New York (1) North Carolina (1)		(1) (1)	(1) (1)	(1) (1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)			68, 443 (1)	552, 411 (1)
Oklahoma (1) Oregon (1)	1)	(1)	(1)	2, 548, 711 (1) (1)	(1)	649, 995 (1)	35, 437 (¹)	214, 463 (¹)			(1) (1)	(1) (1)	(1) (1)	(1) (1)	691, 823	\$6, 289, 116	1, 418, 161 (1) (1)	11, 739, 547 (1) (1)
Pennsylvania 184, 6 Puerto Rico (1) Rhode Island (1) South Dakota 1	1)	, 242, 281 (1) (1)	59, 918 5, 284 (1)	538, 979 84, 548 (1)	415, 901	2, 908, 349	75, 277	542, 524	(1)	(1)	23, 324	189, 952 (¹)	(1) 4, 836 (1)	(1) 77, 148 (1)	(1)	(1)	1, 030, 156 10, 178 (1)	7, 708, 095 162, 796 (1)
Tennessee (1) Texas (1) Utah		(1) (1)	20, 960 21, 189 6, 199	166, 740 191, 958 73, 479	48, 750 8, 277	265, 205 58, 604	110, 059 7, 166	622, 937 47, 531	(1) (1)	(1) (1)	(1) 14, 861 19, 955 329	93, 814 161, 105 4, 664	67, 546 10, 470	423, 738 96, 729	(1)	(1)	269, 566 67, 377 57, 609	
Vermont (1) Virginia 27, 8 Washington (1)	883	(1)	(1) 19, 973 (1)	139, 908 (1)	1, 837 60, 861 (1)	15, 718 389, 286	20, 430 18, 943 21, 943	166, 623 124, 693 231, 308	(1) 1, 399		22, 770 (1)	167, 068 (1)	(1) (1) 54, 591 (1)	351, 086 (1) (1)		1-11-11-1	71, 642 206, 420 55, 864	462, 908 1, 367, 043 623, 766
West Virginia 27, 6 Wisconsin (1) Undistributed 2 68, 4	1) , 459	114, 555 (1) 409, 997		30, 067 154, 680 870, 433		1, 062, 110 1, 330 1, 556, 806					7, 099 (1) 90, 753	44, 522 (1) 629, 259		(1) 3, <b>7</b> 71, 900	(1) 537, 534	(1) 4, 528, 518 10, 817, 634	422, 481 63, 801 369, 366	2, 879, 509 499, 279 2, 772, 206

<sup>1</sup> Included under "Undistributed."

<sup>2</sup> Includes items entered as (1).

1305 LIME

Agricultural lime and other liming materials sold or used by producers in the United States, 1941-42, by kinds

	1941 - 1942							
Kind	Short	tons	Valu	ie	Shor	tons	Valu	1e
	Gross	Effective lime content 1	Total	Aver- age	Gross	Effective lime content 1	Total	Aver- age
Lime: Quicklime Hydrated lime Limestone Calcareous marl	161, 063 221, 664 119, 079 11,909,640 183, 009	136, 900 155, 170 55, 970 5, 597, 530 76, 860	\$866, 721 1, 520, 324 424, 096 14,395,831 175, 393	\$5.38 6.86 3.56 1.21 .96	184, 678 215, 953 3 111, 350 13,745,400 194, 878	156, 980 151, 170 3 52, 340 6, 460, 340 81, 850	\$950, 374 1, 568, 579 3 474, 119 16,993,254 135, 046	\$5. 15 7. 26 3 4. 26 1. 24 . 69

Effective lime contents as follows: Quicklime, 85 percent; hydrated lime, 70 percent; limestone and oyster shells, 47 percent; calcareous marl, 42 percent.
 Figures supplied by Fish and Wildlife Service.
 Preliminary figure.

Building lime.—Production of lime for all building purposes declined sharply from 1941. The degree of slump, however, was more marked for finishing and mason's lime than in lime used to make prepared masonry mortars.

Chemical and industrial lime.—Of the principal chemical uses of lime, only the paper, tannery, and insecticide, fungicide, and disinfectant uses required less lime than in 1941. In paper, the decline resulted from reduced activity in that industry owing primarily to a shortage of wood for pulping.

#### HYDRATED LIME

Production of hydrated lime had increased each year from 1938 through 1941, but the output in 1942 was sharply lower than in 1941. The degree of change was much more severe than that customarily shown in year-to-year fluctuations in demand for hydrated lime.

The 1942 output of hydrated lime was obtained from 165 active plants in 35 States and 2 Territories; production increased over 1941 in 10 States and 2 Territories, decreased in 20 States, and was relatively unchanged in 3 States. In 1942 no production was reported in South Dakota, and the manufacture of the hydrate was started in Louisiana and Oregon. Ranking States, in order of tonnage, were Ohio, Pennsylvania, and Missouri, which together supplied 58 percent of the total.

Uses.—Consumption of hydrated lime was lower in all its principal uses except water purification.

## TRENDS IN PRINCIPAL USES

Trends in major uses of lime in the 1922-42 period are shown in figure 1 and discussed earlier in this chapter. Figure 2 illustrates clearly the marked changes effected by the war on the percentage distribution of lime in its major uses in 1942 from 1941 and also the more pronounced long-term changes from the 1925-29 period.




FIGURE 2.—Percentage distribution of tonnages and values of lime sold or used in 1925-29 (averages), 1941. and 1942, by major uses.

Hydrated lime sold or used by producers in the United States, 1941-42, by States

		1941	ing Byk	ı <b>1942</b>				
State	Active plants	Short tons	Value	Active plants	Short tons	Value		
Alabama California Florida Georgia Hawaii Illinois Indiana. Maryland Massachusetts Michigan Missouri. New York Ohio. Pennsylvania Puerto Rico South Dakota Tennessee Texas. Virginia Wasshington West Virginia West Virginia Other States 3	7 4 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	31, 370 25, 540 12, 214 9, 748 8, 665 39, 496 24, 826 41, 166 14, 464 179, 425 16, 784 539, 939 250, 733 (1) 698 45, 304 27, 415 74, 810 10, 803 48, 028 46, 086	\$224, 609 261, 622 119, 713 70, 755 136, 475 282, 634 168, 618 169, 349 321, 515 107, 493 1, 054, 833 112, 176 4, 661, 687 1, 955, 757 (1) 348, 539 262, 349 486, 488 96, 474 254, 156 1, 262, 163	8 8 8 4 4 1 1 1 6 3 5 5 5 3 9 9 3 16 6 16 6 (1) 5 35	25, 575 30, 367 11, 295 7, 420 8, 823 31, 366 21, 419 28, 767 41, 154 7, 835 184, 866 17, 686 356, 265 213, 475 5, 248 42, 434 23, 355 62, 453 (1) 34, 473 139, 063	\$209, 270 333, 578 120, 044 52, 810 138, 962 234, 242 145, 486 181, 602 322, 626 59, 762 1, 134, 640 132, 596 2, 979, 928 1, 744, 061 81, 557 322, 088 225, 039 443, 049 (1)		
	166	1, 590, 159	12, 354, 798	165	1, 293, 339	10, 290, 304		

<sup>1</sup> Included under "Other States."

2 By groups of States as follows—1941: Maine (2 active plants), Vermont (2), Rhode Island (1), Connecticut (1), and New Jersey (2), 57,663 short tons valued at \$407,308; North Carolina, (1), Puerto Rico (1), Arkansas (2), and Oklahoma (3), 28,195 tons, \$255,568; Wisconsin (6) and Minnesota (2), 24,912 tons, \$192,551; and Colorado (1), Utah (2), Arizona (2), Nevada (2), and Montana (1), 53,316 tons, \$406,738. 1942: Maine (2), Vermont (2), Rhode Island (1), Connecticut (1), and New Jersey (3), 53,086 tons, \$381,529; North Carolina (1), Louisiana (1), Arkansas (2), and Oklahoma (3), 31,374 tons, \$294,885; Wisconsin (7) and Minnesota (2), 22,776 tons, \$173,587; Colorado (1), Utah (2), and Arizona (2), 12,130 tons, \$157,508; and Nevada (1), Montana (1), Washington (2), and Oregon (1), 19,697 tons, \$208,003.

Hydrated lime sold or used by producers in the United States, 1941-42, by uses

		1941		1942					
Use.	Short tons	Val	ie .	Short tons	Val	ue			
	Short tons	Total	Average	51101 € 10113	Total	Average			
Agricultural Building	221, 664 780, 328	\$1, 520, 324 6 665, 319	\$6. 86 8. 54	215, 953 522, 034	\$1, 568, 579 4, 528, 889	\$7. 26 8. 68			
Chemical and industrial: Brick, sand-lime and slag Brick, silica Frod products Glass Insecticides Metallurgy Paints Paper mills Petroleum Sewage Sugar Tanneries Water purification Other uses	(1) (1) (2, 501 (1) 61, 174 (1) 47, 098 (1) (1) 17, 611 44, 8, 560 256, 739	(1) (1) (1) (1) (1) (1) (2) (2) (2) (3) (2) (1) (1) (1) (1) (1) (1) (1) (1) (1) (1	(1) (1) (2) (3) (4) (4) (1) (6) (6) (1) (1) (1) (1) (1) (1) (1) (2) (2) (3) (4) (4) (5) (6) (6) (7) (7) (8) (8) (9) (9) (9) (9) (9) (9) (9) (9) (9) (9	4, 220 9, 368 10, 133 3, 869 27, 619 4, 369 26, 581 25, 669 9, 898 15, 355 42, 892 170, 164 156, 726	35, 158 78, 608 94, 663 27, 492 379, 919 250, 957 36, 857 186, 012 234, 865 70, 252 193, 740 304, 901 1, 267, 167 1, 032, 305	8. 33 8. 39 9. 34 7. 09 7. 84 9. 09 8. 44 7. 00 9. 15 7. 10 12. 62 7. 11 7. 45 6. 59			
현 그는 양주 항 - 트립스의	588, 167	4, 169, 155	7.09	555, 352	4, 192, 836	7. 55			
Total hydrated lime	1, 590, 159	12, 354, 798	7.77	1, 293, 339	10, 290, 304	7. 96			

<sup>1</sup> Included under "Other uses."

The fairly close correlation of refractory lime with steel-ingot production in the 1932–42 period is presented in figure 3. The discordance in recent years between the metallurgical-lime and steel-production curves results partly from increased consumption of lime in the Bayer alumina process and partly from increasing requirements per ton of steel owing to the lower quality of scrap used and the wider use of ore in place of scrap.




Figure 3.—Indicated annual consumption of metallurgical and refractory lime compared with steel production, 1932-42. (Index numbers of steel production by Federal Reserve Board.)

#### SHIPMENTS

#### TOTAL SHIPMENTS

The accompanying tables show supplies of lime available, by States and shipments, from and into groups of States that comprise approximate freight-rate zones.

HYDRATED LIME

Distribution of hydrated lime into groups of States from all producing plants and from all Ohio plants are listed in the adjoining table.

Lime supplies available in continental United States in 1942, by States, in short tons

	a., .				Supply	
State	Sales by producers	Shipments from State 1	Shipments into State	Quicklime	Hydrated lime	Total
Alabama	330, 552	80, 376	49, 771	288, 383	11, 564	299, 94
Arizona	59, 033	15, 577	1, 418	41, 971	2, 903	299, 94 44, 87
Arkansas	(2)	(2)	(3)	36, 823	5, 253	
California	83, 399	(2) 10, 781	26, 854	66, 651	32, 821	42,07
Colorado	(2)	(2), 731	(2)	40, 564	4, 179	99, 47 44, 74
Connecticut	(2)	(2)	(2)	21, 347	14, 859	36, 20
Delaware		()	52, 887	37, 349	15, 538	52, 88
Delaware District of Columbia			15, 814	5, 741	10, 073	
Florida	21, 510		36, 650	38, 809		15, 81
Georgia	10, 824	1, 312	67, 256	53, 880	19, 351	58, 16
rdoho		1,012	2, 134		22, 388	76, 76
Illinois	314,078	127, 568	253, 011	557 261 504	1, 577	2, 13
Indiana	102, 757	81, 515	253, 011 183, 017	361, 594	77, 927	439, 52
Idaho		01, 010		172, 161	32,098	204, 25
Kansas			54, 107	41,080	13, 027	54, 10
Kentucky			30, 733	14, 499	16, 234	30, 73
Louisiana			163, 391	150, 213	13, 178	163, 39
Moino	(2)	(2) (2)	(2) (2)	82, 270	16, 801	99, 07
Maine Maryland	(2)			64, 768	10, 659	75, 42
Massachusetts		16, 246	123, 740	117, 632	52, 733	170, 36
VI assachusetts	87, 537	56, 912	53, 626	48, 634	35, 617	84, 25
Michigan	58, 283	22, 632	167, 334	151, 497	51, 488	202, 98
Minnesota	(2)	(2)	(2)	84, 516	11,811	96, 32
Mississippi			10, 520	5, 864	4, 656	10, 52
Missouri	853, 020	562, 124	13, 363	214, 463	89, 796	304, 25
Montana	(2)	(2)	(2)	26,600	2, 753	29, 35
Nebraska			8, 215	2, 140	6,075	8, 21
Nevada	(2)	(2)	<b>(2</b> )	33, 926	1,087	35, 01
New Hampshire			8, 518	6,099	2, 419	8, 51
New Jersey	(2)	(2) (2)	(2)	56, 148	92,002	148, 15
New Mexico	(2)	(2)	(2)	13,699	1, 569	15, 26
New York	68, 443	9, 469	331, 087	293, 980	96, 081	390,06
North Carolina	(2)	(2)	(2)	60, 657	28,668	89, 32
North Dakota			12,878	436	12, 442	12, 87
Ohio	1, 418, 161	895, 741	139, 638	567, 154	94, 904	662, 05
Oklahoma	(2)	(2)	(2) (2)	26, 588	17, 097	43, 68
Oregon	(2)	(2)	(2)	16, 332	5, 592	21, 92
Pennsylvania	1, 030, 156	387, 904	512, 720	974, 894	180, 078	1, 154, 97
Rhode Island	(2)	(2)	(2)	6, 039	5, 323	11, 36
South Carolina			23, 763	14, 364	9, 399	23, 76
South Dakota	(2)	(2)	(2)	3, 233	1, 723	4.95
rennessee	269, 566	234, 058	8,665	23, 735	20, 438	44, 17
Γexas	67, 377	12, 836	8, 519	39, 974	23, 086	63, 06
Utah	57, 609	940	1, 820	51, 669	6, 820	58, 48
Vermont	71, 642	40, 509	393	30, 771	755	31, 52
Virginia	206, 420	141, 299	72, 048	94, 357	42.812	137, 16
Washington	55, 864	17, 887	2, 428	34, 509	5, 896	40, 40
West Virginia	422, 481	387, 456	183, 325	202, 244	16, 106	218, 35
Wisconsin	63, 801	29, 331	59, 400	67, 649	26, 221	
Wyoming	00, 001	20,001	1,078	131		93, 87
Undistributed 3	369, 366	95, 501	519, 021	131	947	1, 07
j	6, 084, 750	3, 227, 974	3, 199, 142	4, 788, 594	1, 267, 324	6, 055, 91

Includes 28,832 tons unclassified as to destination.
 Included under "Undistributed."
 Includes items entered as "(2)."

Lime shipped (supply) in continental United States in 1942, by origin and destination of shipments, in short tons

							O	rigin							
Destination	Illinois	s, Indian gan, Oh	a, Michi- io	New		Jersey, Pennsyl- ginia		sachu le Island			, Georgia lina, Vir			ma, Lou Fennesse	
	Quick- lime	Hy- drated lime	Total	Quick- lime	Hy- drated lime	Total	Quick- lime	Hy- drated lime	Total	Quick- lime	Hy- drated lime	Total	Quick- lime	Hy- drated lime	Total
Illinois, Indiana, Michigan, OhioDelaware, District of Columbia, Maryland, New Jersey, New York, Pennsylvania,	949, 587	200, 022	1, 149, 609	47, 355	6, 128	53, 483	132	1	133	10, 623	1, 747	12, 370	704	1, 329	2, 033
West Virginia.  Connecticut, Maine, Massachusetts, New Hampshire, Rhode Island, Vermont.	370, 808 9, 359	117, 141 17, 742	487, 949 27, 101	1, 152, 755	301, 961	1, 454, 716	26, 057	16, 449	42, 506	89, 895	100	111, 688	23, 052	1, 195	24, 247
Florida, Georgia, North Carolina, South Carolina, Virginia. Alabama, Kentucky, Louisiana, Missis-	6, 481	29, 661	36, 142	55, 319 28, 362	4, 988 9, 897	60, 307 38, 259	112, 630 200	46, 343 18	158, 973 218	350 57, 181	264 55, 098	614 112, 279	157, 027	27, 288	184, 315
sippi, Tennessee. Arkansas, Kansas, Nebraska, Oklahoma, Texas. Iowa, Minnesota, Missouri, Wisconsin	61, 018 1, 125 68, 663	15, 626 2, 414 25, 184	76, 644 3, 539 93, 847	37	187 50 5	224 50 5		7	7		1, 186	1, 186 43	351, 928 87	35, 575	387, 503 87
Arizona, California, Colorado, Idaho, Mon- tana, Nevada, New Mexico, North Da- kota, Oregon, Sonth Dakota, Utah, Washington, Wyoming	3, 559	8, 721	12, 280	-											

Lime shipped (supply) in continental United States in 1942, by origin and destination of shipments, in short tons—Continued

				1		Or	igin	p. y				
Destination	Arkansa	s, Oklahon	na, Texas	Minnesota, Missouri, Wisconsin			Arizona, rado, New South Washin	Montana, Mexico, Dakota,	Nevada, Oregon,	United States		
	Quick- lime	Hy- drated lime	Total	Quick- lime	Hy- drated lime	Total	Quick- lime	Hy- drated lime	Total	Quick- lime	Hy- drated lime	Total
Illinois, Indiana, Michigan, Ohio		132	132	244, 005	47, 058	291, 063				1, 252, 406	256, 417	1, 508, 823
Delaware, District of Columbia, Maryland, New Jersey, New York, Pennsylvania, West Virginia.		12	, 12	25, 421	4, 060	29, 481				1, 687, 988	462, 611	2, 150, 599
Connecticut, Maine, Massachusetts, New Hamp- shire, Rhode Island, Vermont					295	295				177, 658	69, 632	247, 290
Florida, Georgia, North Carolina, South Carolina, Virginia		520	520	12, 816	636	13, 452				262, 067	123, 118	385, 185
Alabama, Kentucky, Louisiana, Mississippi, Ten- nessee. Arkansas, Kansas, Nebraska, Oklahoma, Texas. Iowa, Minnesota, Missouri, Wisconsin.	28, 435 83, 569 687	5, 931 41, 403 662	34, 366 124, 972 1, 349	109, 047 35, 243 338, 358	8, 125 23, 878 114, 961	117, 172 59, 121 453, 319				550, 465 120, 024 407, 708	66, 637 67, 745 140, 855	617, 102 187, 769 548, 563
Arizona, California, Colorado, Idaho, Montana, Nevada, New Mexico, North Dakota, Oregon, South Dakota, Utah, Washington, Wyoming	1, 087	1, 644	2, 731	5, 128	8, 629	13, 757	320, 504	61, 315	381, 819	330, 278	80, 309	410, 587

Shipments of hydrated lime from plants in continental United States and in Ohio in 1942, by destinations

LIME

	From all	plants	Fron	n Ohio p	lants
Destination	Short tons	Distri- bution (per- cent)	Short tons	Distri- bution (per- cent)	Percent of total ship- ments
Illinois, Indiana, Michigan, Ohio	256, 417 462, 611	20 36	156, 412 116, 224	44 33	61 25
Connecticut, Maine, Massachusetts, New Hampshire, Rhode Island, Vermont	69, 632 123, 118	6 10	17, 742 29, 661	5 8	25 24
Florida, Georgia, North Carolina, South Carolina, Virginia. Alabama, Kentucky, Louisiana, Mississippi, Tennessee	66, 637	5	11, 552	3	17
Arkansas, Kansas, Nebraska, Oklahoma, Texas	67, 745	5	2, 414	ĭ	4
Iowa, Minnesota, Missouri, Wisconsin.  Arizona, California, Colorado, Idaho, Montana, Nevada,	140, 855	11	13, 464	4	10
New Mexico, North Dakota, Oregon, South Dakota, Utah, Washington, Wyoming	80, 309 11, 944	6 1	8, 602 194	(1)	11 2
	1				

<sup>1</sup> Less than 0.1 percent.

#### **PRICES**

Average values for total sales of building quicklime are higher than for building hydrate, an anomalous condition compared with values of types of agricultural and chemical lime. This condition results principally from the rather widespread use of the relatively higher-priced pulverized quicklime in building. It also is noteworthy that some producers in nearly all sections of the country generally obtain a higher price for bulk quicklime than for bulk hydrate for all uses, although the most common practice is to set a higher value on the hydrate.

#### **NEW DEVELOPMENTS**

A new type <sup>1</sup> of limekiln designed to calcine small sizes of stone was introduced in 1942.

Descriptions <sup>2</sup> of the properties and methods of manufacture of dead-burned, stabilized, and enriched dolomite-base refractories were published.

## PLANT CAPACITY

In 1942 about 72 percent of total capacity (based upon a 300-operating-day year) was used in the country. Data on capacities of calcining equipment (excluding obsolete units) are listed in the following table, by types and districts.

<sup>1</sup> Ellerbeck, T. R., Vertical Kiln of New Design Calcines Smaller Sizes of Crushed Limestone: Pit and Quarry, vol. 34, No. 11, May 1942, pp. 55-58.
2 Schallis, Alvin, Dolomite-Base Refractories: Bureau of Mines Inf. Circ. 7227, 1942, 11 pp.

# Capacities and number of kilns in active lime plants in the United States in 1942, by types and status of kilns and by districts

			Pot	kilns			Shaft	kilns			Rotar	y kilns		Tota	ıl capacit	V nor
District	Active	Ac	tive	Ina	ctive	Ac	tive	Ina	ctive	Ac	tive	Inac	ctive		4-hour da	
District .	plants	Num- ber	Capacity 1 (short tons)	Num- ber	Capacity 1 (short tons)	Num- ber	Capacity 1 (short tons)	Num- ber	Capacity 1 (short tons)	Num- ber	Capacity 1 (short tons)	Num- ber	Capacity 1 (short tons)	Active (short tons)	Inac- tive (short tons)	Total (short tons)
Maine, Rhode Island, and Connecticut— Massachusetts, Vermont, and New York Pennsylvania and New Jersey— Maryland— Virginia— North Carolina, Georgia, and Florida— Alabama——————————————————————————————————	14 14 65 11 25 6 9 18 23 17 14 10 14	(2) 154 7 62 20 23 (2) 5	(2) 687 7 584 218 319 (2) (2)	(3) 18 12 (3) (4)	(3) 76 92 (3) (4)	18 4 50 99 (8) 71 21 9 56 67 275 41 4 9 32 61 9 40	281 4 557 1, 156 (*) 729 132 • 1, 245 936 2, 966 4 • 554 1, 385 • 1, 108 549 280	10 \$ 23 12 \$ 18 7 7 6 \$ 13 100 16 \$ 31 10 5	122, \$ 262 127 \$ 301 \$ 410 115 \$ 179 \$ 945 \$ 369 \$ 10 165 \$ 195 \$ 80 132	(2) 9 21 10 (2) 8 (2) 7 7	(2) 982 2,465 715 (2) 1,260 (2)	(9)	(3)	281 1, 177 3, 660 584 947 1, 245 2, 237 5, 434 1, 451 554 2, 645 1, 108	122 262 203 92 301 54 115 179 945 285 369 165 195	403 1, 439 3, 863 676 1, 248 1, 360 2, 416 6, 379 1, 736 2, 810 1, 303 1, 080 912
Summary	11 269	280	1, 953	60	608	902	11, 763	10 239	10 2, 891	103	9, 697	(3)	(3)	23, 413	3, 499	26, 912

<sup>1</sup> Expressed as output of quicklime per 24-hour day.
2 Included with data on active shaft kilns.
3 Included with data on inactive shaft kilns.
4 Includes data on active pot kilns.
5 Includes data on inactive pot kilns.
6 Includes data on active sintering machines.
7 Includes data on active shaft kilns.
8 Included with data on active pot kilns.
9 Includes data on active rotary kilns.
10 Includes data on active rotary kilns.
10 Includes data on inactive rotary kilns.
11 A plant in California with only hydrating equipment is not included in this total

LIME 1313

#### SIZE OF PLANTS

There has been a strong trend toward larger lime plants, as is shown by comparison of data on size groups in 1942, the year of record production, with those in 1925, the preak production year of the 1920's. In all groups under 25,000 tons, both the number of plants and the percentage of total output from each group declined sharply. The number of plants in all groups over 25,000 tons increased, and the percentage of total output increased for each group except the group 50,000 and less than 100,000 tons. The largest gain in percentage of total production was in the group over 100,000. The marked decline in total number of plants from 1925 took place entirely in the groups under 25,000 tons. These data on size of lime plants are not comparable with those on companies and plants published in these chapters in recent years. The earlier studies are based only upon size of companies.

Distribution of lime (including refractory) plants in 1925 and 1942, according to size of production

		1925			1942	
Size group (short tons)		Produ	ction		Produ	ction
	Plants	Short tons	Percent of total	Plants	Short tons	Percent of total
Less than 1,000	172 86 65 81 24 19	40, 054 246, 433 478, 336 1, 230, 411 805, 807 1, 398, 246 381, 536	1 5 10 27 18 31 8	48 72 28 49 39 21	17, 844 195, 265 192, 497 802, 353 1, 383, 782 1, 441, 995 2, 070, 055	1: 2: 24 34
	450	4, 580, 823	100	270	6, 103, 791	100

#### FOREIGN TRADE

Because of wartime restrictions, no figures on imports and exports can be published. However, foreign trade of the United States in lime has a negligible effect on the domestic industry.

Imports.—During the 1935-39 period, annual imports of lime (including dead-burned dolomite) averaged 14,108 short tons valued at \$240,909. This represents only 0.4 percent of average annual domestic production of 3,692,397 tons during 1935-39. In 1940, the last year for which data are complete, 9,205 tons of lime valued at \$81,888 were imported or only 0.2 percent of domestic output. The principal volume of imports is from British Columbia, Canada, into the the Pacific Coast States, a flow in 1940 that comprised 98 percent of the total. Imports increased in 1941 and for the January-September period were at a monthly rate of 1,018 tons, which was 33 percent above the rate (767 tons) of 1940. Imports doubtless increased in 1942 over 1941, owing to shortages of lime on the West Coast, which were overcome by bringing in Canadian material.

Exports.—Annual exports of lime in the 1935-39 period averaged 10,905 tons valued at \$123,167—a volume that represented only 0.3 percent of the average annual domestic production of 3,692,397

tons during the same period. During 1940 a new record of 31,912 tons (0.7 percent of domestic output of lime) was exported. The volume of exports increased further in 1941 and for the January-September period was at a monthly rate of 3,605 tons—a 36-percent gain over the monthly rate (2,659 tons) of 1940. Exports in 1942 undoubtedly advanced over 1941 owing to expanding markets in the Latin American countries and in eastern Canada.

# **CLAYS**

# By G. W. Josephson and A. Linn 1

#### SUMMARY OUTLINE

	Page	[8] A. Santa,	Page
General summary	•	Bentonite	1323
Salient statistics		Fuller's earth	1324
Consumption and uses	1317	Miscellaneous clays	1326
China clay or kaolin Ball clay	1318	Clay products	1327
Fire clay	1320	Technologic developments	1328

#### GENERAL SUMMARY

The reaction of the various segments of the clay industry to wartime conditions emphasizes the fact that, although there is considerable overlapping in many fields, the physical properties of the various clays have enabled each clay to dominate one or more specialized markets. Production of some clays increased while others decreased, depending on the extent to which each contributed to an increasingly military economy. Shipments of fire clay have nearly doubled since 1940, and even those clays that declined from 1941 held at levels comparing favorably with recent peacetime years. Over-all, 4 percent more merchant clay was shipped in 1942 than in 1941.

As clays are available in more than ample quantities, no restrictions in their use were imposed by the War Production Board; in fact, their application as substitute materials was encouraged. Many examples of such substitute products appeared, but the total consumption of

clay in them was insignificant.

The restrictions felt by the clay industry were those that developed from wartime shortages in such things as metals, equipment, and labor. Only fire clay was regarded as critical enough to warrant granting special priority ratings for repair and expansion programs. As time went on, labor became increasingly scarce. In isolated instances plants reported that they could not maintain sufficient production to fill all orders; but, in general, reduced crews met the sales demand. Shortages of hardware, plumbing, and lumber led to allocations of available supplies to war construction and discouraged a general private-building program. Transportation was a problem in many areas. Under the stress of accumulated difficulties, a few plants suspended operation for the duration of the war; but the great majority, although granted no advantages, found ways of solving their problems and maintained production.

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce. Domestic figures for fuller's earth compiled by R. W. Metcalf, of the Bureau of Mines.

Prices of all clays were under the jurisdiction of the Office of Price Administration. The General Maximum Price Regulation froze prices at the maximum levels of March 1942. Many producers complained that various expenses, such as costs of labor, transportation, and repair parts, had risen since their prices were established, and a few petitioned the Office of Price Administration for relief. Some of the cases were under consideration at the end of the year, but none had been approved.

Foreign trade in clays was reduced materially during 1942. Imports consisted principally of kaolin and ball clay from the United Kingdom, and exports (which totaled 193,199 tons) were 61 percent fire clays.

Interest in clay as an ore of aluminum reached a point at which large sums of money were expended by both private concerns and Government agencies in research and exploration programs. velopment may prove to have primary importance in the future, although many obstacles must be overcome before clays will be able

to compete with bauxite upon an equal basis.

Bureau of Mines statistics reported in this chapter are limited to those tonnages of clay that are sold or shipped raw by the producer. Any departures from this rule are clarified in the text. The tonnages do not include the much greater quantity of clay mined by manufacturers of brick and other clay products at integrated plants at mine or pit.

Salient statistics of the clay industry in the United States, 1925-42

	1925–29 (average)	1930–34 (average)	1935–39 (average)	1940	1941	1942
Domestic clay sold or used by pro-						1 327
ducers: Kaolin, china clayshort tons	453, 618 116, 127	431, 932 70, 299	654, 147 108, 525	833, 450 140, 707	1, 087, 848 198, 445	
Fire clay 1 (including stoneware clay) short tons.  Bentonite do Fuller's earth do	2, 898, 576 (2) 261, 640	84, 762 259, 354	188, 385 204, 529	251, 032 146, 568	354, 028 207, 446	4, 839, 332 374, 967 204, 244
Miscellaneous clays 1do	<sup>2</sup> 575, 708	305, 973	360, 602	710, 515	1, 210, 168	1, 019, 663
Total domestic: Quantitydo Value	4, 305, 669 \$17, 568, 812	2, 639, 684 \$10, 977, 776	3, 691, 497 \$15, 455, 392	4, 847, 519 \$19, 633, 568	7, 225, 502 3\$27,037,391	7, 547, 087 \$26, 662, 897
Imports: Kaolin or china clay_short tons Common blue and Gross-Almer-	339, 014	140, 888	122, 232	105, 567		
ode short tons. Fuller's earth do Other clay do	12, 130 8, 118 61, 048	4,708	2, 256	474	342	287
Total imports: Quantitydo Value	420, 310 \$3, 841, 462					
Exports: Fire clayshort tons_	55, 316	39, 709	61, 247	96, 501	91, 732	118, 101
Other clay (including fuller's earth) short tons	54, 028	68, 978	87, 824	87, 667	116, 120	75, 098
Total exports: Quantitydo Value	109, 344 \$1, 217, 769	108, 687 \$1, 323, 744				193, 199 <b>\$2,</b> 042, <b>94</b> 0

Does not include clay burned into clay products in integrated plants at mine or pit.
 Sales of bentonite included under "Miscellaneous clay" before 1930.
 Revised figures.

## CONSUMPTION AND USES

The accompanying table gives sales of specified domestic clays by kinds and uses in 1942, continuing a series begun in 1921. Of particular interest in 1941 and 1942 have been the sharp increase in refractory and foundry clays, the apparent recovery in fuller's earth, and the decrease in rubber clay.

Figure 1 shows the contributions of the clays to refractory uses

during the past 10 years.




FIGURE 1.—Trends in sales of clay by domestic producers for use in refractories, 1933-42.

Clay sold or used by producers in the United States in 1942, by kinds and uses, in short tons

Use	Kaolin	Ball clay	Fire clay and stoneware clay	Ben- tonite	Miscel- laneous clay, includ- ing slip clay	Fuller's earth	Total
Pottery and stoneware: Whiteware, etc. Stoneware, including chemical	86, 029	136, 181	10, 215				232, 425
stoneware		957 894 300	42, 067 4, 649		5, 381 506		43, 024 10, 924 806
Tile, high-grade	86, 029 12, 313	138, 332 9, 793	56, 931 3, 051		5, 887 60		287, 179 25, 217
Kiln furniture, etc.: Saggers, pins, stilts Wads	2, 348	1, 357 239	46, 170 9, 816				49, 875 10, 055
Architectural terra cotta	2, 348	1, 596 75	55, 986 10, 390				59, 930 10, 465

Clay sold or used by producers in the United States in 1942, by kinds and uses, in short tons—Continued

i grand i sa <b>Use</b> Angle Language un angle sa sa sa sa sa sa sa sa sa sa sa sa sa	Kaolin	Ball clay	Fire clay and stoneware clay	Ben- tonite	Miscellaneous clay, including slip clay	Fuller's earth	Total
Paper:	t 24,13	10.00	1344				4.
Filler Coating	364, 154 192, 819	1, 200	583		<u> </u>		365, 937 192, 819
	556, 973	1, 200	583	vadbe -	18 A September 1		558, 756
Rubber Linoleum and oilcloth	51, 334 6, 304	6, 000	5,000 11,434				56, 334 23, 738
Paints: Filler or extender Calcimine	15, 289 1, 403	238	122				15, 649 1, 403
Cement manufacture	16, 692 12, 315	238	122 2, 259	3, 614	287, 639		17, 052 305, 827
Refractories: Fire brick and block Bauxite, high-alumina brick	149, 996	1,000	3, 105, 621 77, 478		8, 605		3, 265, 222 77, 478
Fire-clay mortar, including clay processed for laying fire brick. Clay crucibles. Glass refractories	2,832 396 475	500 175	309, 732 1, 203 21, 996		33		312, 597 2, 099 22, 646
Zinc retorts and condensers Foundries and steelworks	6, 187	500 100	45, 351 815, 026	149, 384		297	45, 851 995, 841
	159, 886	2, 275	4, 376, 407	149, 384	33, 485	297	4, 721, 734
Miscellaneous:  Rotary-drilling mud  Filtering and decolorizing oils			763	48, 912	118, 423	2, 049	170, 147
(raw and activated earths) Other filtering and clarifying				Section .		7, 730	310, 660 7, 730
Artificial abrasives Asbestos products Chemicals	290 677 5, 130	282 500	1, 377 256 20, 423		4, 206		6, 155 1, 433 25, 553
Filler (other than paper or paint)  Plaster and plaster products  Concrete admixture, sealing	596 250	1,000		3, 562	18,070	98	1,000 22,326 250
dams, etc Heavy clay products			287, 520	3, 013	527, 276		3, 013 814, 796
Other uses	35, 451 42, 394	1,002 2,784	6,830	49, 668 221, 969	692, 592	203, 947	117, 792
Grand total:		=			<b></b>		
1942	946, 588 1, 087, 848	162, 293 198, 445	4, 839, 332 4, 167, 567	374, 967 354, 028	1, 019, 663 1, 210, 168	204, 244 207, 446	7, 547, 087 7, 225, 502

<sup>&</sup>lt;sup>1</sup> Comprises following: Mineral oils, 172,518 short tons; vegetable oils, 21,328 short tons.

#### CHINA CLAY OR KAOLIN

Shipments of kaolin or china clay by domestic producers were 13 percent lower in both quantity and value in 1942 than in the record year 1941. Although this might be interpreted as indicating a period of recession, further comparisons show that activity was high. More domestic kaolin was shipped in 1942 than in any previous year except 1941, 14 percent more than in 1940, and 45 percent more than the average in the years 1935–39.

Mine shipments were reported in 14 States, but most of the tonnage came from Georgia and South Carolina. Georgia, furnishing 79 percent, contributed an even greater portion of the national total than usual, and South Carolina ranked second with 12 percent.

CLAYS 1319

三人 日本を持ちているいかと

Outstanding changes in kaolin consumption compared with 1941 were the 60-percent reduction in its use in rubber, 16-percent in pottery, and 8-percent in paper and the 30-percent increase in refractories. The drastic decline in sales to the rubber industry was a direct result of the rubber shortage, but recovery in this use is to be expected if synthetic rubber technology does not require the use of materials that will displace clay. Although pottery requirements were not as great as in 1941, shipments in 1942 compare favorably with those in previous years. As paper clays constitute approximately 60 percent of the total kaolin tonnage, even the 8-percent reduction resulting in part from a paper-production curtailment order by the War Production Board constituted a serious loss. However, comparisons show that kaolin sales to the paper industry were greater in 1942 than in any prior year except 1941. Wartime expansion of the high-temperature manufacturing processes sharply stimulated consumption of kaolin in refractories.

In addition to shipments of raw kaolin, producers reported to the

Bureau of Mines that 194,234 tons were burned into clay products

at the mine or pit.

Although kaolin is not yet a commercial source of aluminum metal,

many deposits were investigated as possible sources.

Kaolin beneficiation plants equipped to recover mica as a byproduct of clay production enjoyed a very active market during 1942. During the latter part of the year a shortage of ground mica developed, and a movement was initiated to obtain price concessions from the Office of Price Administration to stimulate production.

Crude undried kaolin sold as low as \$2.50 per ton for refractory uses, and processed grades sold all the way up to \$20 for air-floated enamel quality. Specialties were listed at \$20 to \$40 per ton. Most paper clays ranged from \$7.50 to \$15 and rubber clays from \$8.50 to \$20 per ton. The national average value, as reported by producers to the Bureau of Mines, was \$8.49 per ton, or slightly higher than the \$8.46 in 1941 and \$8.39 in 1940.

Kaolin sold or used by producers in the United States, 1940-42, by States

State	19	40	19	41	1942		
	Short tons	Value	Short tons	Value	Short tons	Value	
Alabama California Delaware Florida Georgia Illinois Maryland North Carolina Pennsylvania South Carolina Tennessee Utah Vermont Virginia Undistributed <sup>2</sup>	(1) 14, 407 (1) 570, 010 (1) 49, 541 152, 227 (1) (1) (1) (1) (2)	(1) \$118, 481 (1) (1) (4, 834, 826 (1) 202, 642 169, 981 1, 302, 812 (1) (1) (1) (1) 365, 364	(1) 20, 810 (1) 787, 013 (1) 44, 277 177, 276 (1) (1) (1) (2) (3)	(1) \$164, 110 (1) (6, 573, 605 (1) (1) (1) (1) (1) (1) (1) (1) (1) (1)	(1) 237 (1) 744, 408 (1) (1) 19, 862 115, 679 (1) (1) (1) (1) (1) (1) (1) (1) (1) (1)	(1) \$119,004 (1) (1) (1) (1) (1) (1) (1) (1) (1) (2) (1) (2) (1) (1) (1) (1) (1) (1) (1) (1) (1) (1	
	833, 450	6, 994, 106	1, 087, 848	9, 205, 892	946, 588	8, 037, 233	

Included under "Undistributed."
 Includes States indicated by "(1)" above.

Imports of china clay in 1942 totaled 63,278 tons valued at \$671,081, 26 percent less than the 85,141 tons valued at \$901,973 received in 1941; the United Kingdom supplied 62,774 tons, and the remainder (504 tons) came from Canada. The English clay was valued at \$10.59 per short ton, approximately the same as in 1941, but transportation added materially to the delivered price in this country. Trade journals quoted lump clay, f. o. b. American ports, c. i. f., at \$19 to \$28 and air-floated at \$40 to \$60 per long ton.

Kaolin exports are not recorded separately by the Department of Commerce, but producers reported to the Bureau of Mines that in 1942 they exported a total of 2,128 tons valued at \$19,216 to Canada,

Mexico, and South America.

Georgia kaolin sold or used by producers, 1938-42, by uses

	China cl	ay, paper cla	y, etc.	e. Refractory uses			Total kaolin			
Year		Value			Val	ue		Valt	10	
ieat	Short tons	Total	Aver- age per ton	Short tons	Total	Aver- age per ton	Short tons	Total	Aver- age per ton	
1938	367, 612 450, 121 497, 881 669, 978 594, 780	\$3, 199, 169 3, 956, 344 4, 625, 080 6, 216, 087 5, 645, 760	\$8.70 8.79 9.29 9.28 9.49	45, 020 62, 093 72, 129 117, 035 149, 628	\$115, 749 179, 383 209, 746 357, 518 490, 471	\$2. 57 2. 89 2. 91 3. 05 3. 28	412, 632 512, 214 570, 010 787, 013 744, 408	\$3, 314, 918 4, 135, 727 4, 834, 826 6, 573, 605 6, 136, 231	\$8.00 8.00 8.40 8.30 8.20	

#### BALL CLAY

Compared with 1941, total sales of ball clay decreased 18 percent in 1942 in both tonnage and value, but in spite of this reduction they were the second highest on record. Approximately 49 percent of the total in 1942 was mined in Kentucky and 43 percent in Tennessee; the remainder came principally from Maryland and New Jersey. Mississippi and Missouri reported minor quantities and Nevada none.

Imports of "common blue and ball clays, unwrought and unmanufactured" from the United Kingdom fell to 19,648 short tons in 1942, or 27 percent from the 26,817-ton total for the previous year. The average value was \$9.21 per ton compared with \$9.06 in 1941. Thirty-four tons valued at \$885 were received from Brazil and 102 tons valued

at \$903 from Canada.

During recent years domestic producers have improved and standardized the quality of their product to a degree that has gained its acceptance in the field formerly held by foreign ball clays. In prewar years domestic ball clay could be laid down at consumers' plants at a lower price than imported; this advantage was an even greater factor in 1942, when ocean freight rates were excessively high. Displacement of the entire foreign tonnage is unlikely, however, as strenuous efforts are being made by English clay producers to retain their position in the American market.

The average value of domestic ball clay as reported to the Bureau of Mines by producers was \$8.49 per ton, slightly higher than the \$8.45 of 1941 and substantially more than the \$7.57 realized in 1940. Prices were limited by the General Maximum Price Regulation, and

trade-journal quotations listed bulk, shredded, at \$3 to \$8.25 and air-

floated, in bags, at \$10 to \$18.25.

War conditions stimulated consumption in refractories, kiln furniture, and paint filler. Decreased amounts were required for products devoted principally to the needs of the civilian economy, such as pottery, paper filler, and linoleum, but these requirements compared favorably with consumption in the same categories in most pre-war years. Eighty-five percent of the domestic ball clay shipped in 1942 was used in whiteware or cream-color ware and 6 percent in high-grade tile.

Ball clay sold by producers in the United States, 1940-42, by States

	19	40	19	41	1942		
State	Short tons	Value	Short tons	Value	Short tons	Value	
Kentucky Maryland Mississippi	75, 933 (¹)	\$600, 264 (¹)	105, 586 (1)	\$944, 705	80, 259 (1) (1)	\$696, 788 (1) (1)	
Missouri Nevada New Jersey	(1) (1) (1)	(1) (1) (1) (1) 414, 602	(1) (1) (1) 80, 506	(1) (1) (1) 664, 906	(1) (1) 70, 573	(¹) (¹) 606, 118	
TennesseeUndistributed 2	53, 871 10, 903	50, 566	12, 353	67, 989	11, 461	75, 599	
	140, 707	1,065,432	198, 445	1, 677, 600	162, 293	1, 378, 50	

<sup>1</sup> Included under "Undistributed."

# FIRE CLAY

Intense wartime activity in the metal-working and other hightemperature process industries continued to absorb increasing quantities of refractories. Shipments of domestic fire clay were 16 percent greater in 1942 than in 1941, establishing a new record for that portion of the fire-clay tonnage that is sold or shipped raw to distant plants for further processing or ultimate consumption. In addition to this merchant clay, producers reported that 3,457,413 tons of fire clay were burned into firebrick or other clay products in integrated plants at the mine or pit, 6 percent more than the 3,275,021 tons burned in

At the beginning of the rearmament program, the fire-clay refractories producers, who for years had been operating at less than 50 percent of capacity,<sup>2</sup> had enough active equipment to handle immediate demands. In addition, obsolete and inactive plants and facilities represented a considerable capacity. As the tremendous construction and modernization programs in the steel, coke, magnesium, aluminum, power, glass, and other industries got under way, refractories were supplied as needed with few delays in delivery. The War Production Board gave close attention to the situation, but the establishment of rigid controls did not become necessary. Virtually all that was required was an occasional meeting of a committee representing members of the industry and the War Production Board to relieve some local shortage. As demand increased, more and more obsolete facilities were rehabilitated and improved to meet requirements without construction of new plants. It has been esti-

<sup>&</sup>lt;sup>2</sup> Includes States indicated by "(1)."

Ramsay, John D., Refractories the Backbone of Industry: Penton Press, Cleveland, Ohio, 1941, p. 78, 556250—43——84

mated that, in contrast to the mushroom growth of the consuming industries, only about 10 percent of new capacity in the form of new plants and expansion or modernization of old ones has been added to the refractories industry.3 Although there is some minor amount of unused additional facilities, the industry was considered to be operating at close to capacity at the end of 1942. It is expected that, barring

major production interruptions, all demands can be met.

Shipments of fire clay were reported from 29 States in 1942. though production is widely distributed, the major tonnages are concentrated in relatively few States owing to market and quality factors. Pennsylvania supplied 26 percent of the total, Missouri 23, Ohio 16, California 9, and Kentucky 9; thus, these five States shipped 83 percent. A map showing location of fire-clay mines in the United States was published in the chapter on Clays in Minerals Yearbook, 1941.

Fire clay has a wide variety of uses, many of which in normal times consume substantial quantities, but in 1942 over 90 percent went into refractories.

According to the records of the Department of Commerce, 118,101 tons of fire clay valued at \$709,455 were exported in 1942, principally to Canada, England, and Mexico, compared with 91,732 tons valued This 29-percent increase in fire-clay exports at \$721,627 in 1941. contrasts sharply with the 35-percent reduction in exports of all other clay. It is apparent from these figures that substantial quantities of American clay bolstered the munitions production of our allies.

Fire clay, including stoneware clay, sold or used by producers in the United States, 1940-42, by States

State	194	0	19	41	1942		
	Short tons	Value	Short tons	Value	Short tons	Value	
Alabama California Colorado Illinois Indiana Kentucky Maryland Missouri 3 New Jersey New Mexico Ohio Pennsylvania South Carolina Tennessee Texas Utah Washington West Virginia Other States 4	42, 843 193, 713 52, 695 147, 148 69, 144 289, 090 12, 582 487, 650 91, 325 3, 263 470, 101 794, 702 (*) (4) 12, 498 20, 113 21, 108 55, 853 21, 419	\$74, 868 459, 680 89, 206 308, 711 82, 962 728, 380 767, 479 1, 391, 045 512, 546 10, 928 1, 039, 228 1, 984, 272 (*) (4) 22, 686 40, 107 36, 097 103, 989 94, 562	52, 509 316, 226 84, 986 201, 139 111, 551 17, 790 794, 705 133, 126 (4) 689, 187 1, 130, 525 4, 046 38, 120 31, 646 15, 473 65, 521 70, 885 14, 608	\$108, 703 714, 779 143, 398 448, 002 142, 329 1, 1, 220, 490 99, 229 1, 782, 139 714, 925 (4) 1, 689, 308 2, 848, 049 7, 576 117, 168 45, 880 31, 150 91, 604 133, 300 49, 704	96, 567 433, 571 92, 804 180, 994 77, 597 416, 870 15, 213 1, 110, 962 112, 041 4, 634 790, 489 1, 242, 058 (4) 45, 791 16, 525 70, 468 74, 141 14, 347 4, 839, 332	\$158, 156 999, 901 195, 468 329, 212 95, 072 1, 165, 600 2, 450, 752 639, 794 11, 349 1, 627, 630 30, 82, 851 (4) 166, 046 61, 499 32, 667 108, 674 146, 245 34, 836	

<sup>1</sup> Does not include clay burned into clay products in integrated plants at mine or pit.

<sup>1</sup> Does not include clay burned into clay produces in integrated planes at line of planes.

2 Revised figures.

3 Includes diaspore and burley clay as follows—1940: 34,359 tons valued at \$156,603; 1941: 79,897 tons, \$405,673; 1942: 119,357 tons, \$591,124.

4 Included under "Other States."

5 Includes States indicated by "(\*)" above, and Arkansas, Connecticut (1940), Idaho, Iowa, Massachusetts, Minnesota, Mississippi (1941), Montana (1942), Nebraska, Nevada, North Carolina (1940-41), North Dakota, Oregon, Vermont (1941), and Virginia.

<sup>&</sup>lt;sup>8</sup> Information supplied by personnel of War Production Board.

CLAYS 1323

A CAN THE REAL PROPERTY OF THE PARTY OF THE

Imports of fire clay have not been an important factor in recent years. Facing competition from American fire clays, Gross-Almerode had even in pre-war years declined to a few hundred tons per year. Klingenberg clay was prized by American graphite crucible makers, but it has been largely replaced by American clays. Obviously neither of these German clays was imported in 1942, but suitable domestic substitutes are available.

In 1942 the average value of merchant fire clays—\$2.35 per ton—was somewhat lower than the \$2.44 reported for 1941. Prices were frozen at March 1942 levels by the General Maximum Price Regula-

tion.

#### BENTONITE

Bentonite enjoyed a good market in 1942; output, which increased 6 percent over 1941, reached a new record. Wyoming produced slightly less than in 1941 but was still the leading producer, with 37 percent of the total. South Dakota increased shipments by 54 percent and supplied 24 percent of the total. In 5 years South Dakota has more than quadrupled its bentonite output. Reflecting the high quality of the bentonite from the Wyoming-South Dakota district, its 61 percent of the national tonnage commanded 76 percent of the value. For the entire United States the average value in 1942 was \$6.80 per ton, which compares with \$6.93 in 1941 and \$7.65 in 1940.

Of the 1942 shipments, 40 percent was used in foundries and steel works, 31 percent for filtering and decolorizing oils, 13 percent in oilwell drilling muds, and the remaining 16 percent in a wide variety of applications. Foundry consumption was higher, in line with metal activity. The use of bentonite in foundries, where its bonding properties are valuable, increased from 53,872 tons in 1939 to 149,384 tons in 1942. The decrease in oil-well drilling reduced that market, but requirements for oil filtering held close to the level of 1941.

Some of the principal firms increased their production capacity substantially over that in 1941, but this probably was not a strong factor in reduction of the average value, which likely resulted from the increased proportion of material sold for foundry work—a com-

paratively low-priced grade.

Although some mine-run material is sold as low as about \$2 per ton, in general prices ranged from about \$4 for unprocessed material through various pulverized grades, mainly in the \$7 to \$20 span, to a maximum of about \$35 per ton for extremely finely divided

products.5

In oil refining, bentonite is directly competitive with fuller's earth, as well as with other materials discussed in the fuller's earth section of this chapter. Usually the bentonites and sub-bentonites used for this purpose have little natural bleaching capacity, but when acid-treated or activated they are converted into very effective bleaching agents. As it is often difficult to distinguish between these two clays there has been some reclassification by producers in past years. Although the Bureau of Mines as a rule accepts the producer's classification of his commodity, this type of discrepancy is held to a minimum wherever feasible.

Information furnished by Mica-Graphite Division, War Production Board.
 Information supplied by Office of Price Administration.

The same is often true of those clays used as rotary-drilling muds. For this use, clays having bentonitic characteristics have particular value for suspending cuttings and maintaining a desirable specific gravity. The boundary between bentonite and other clays of somewhat similar properties is sometimes hazy, and drilling muds that are not obviously bentonite are classed among the miscellaneous clays.

Exports, as reported by producers to the Bureau of Mines and excluding foreign shipments made by dealers and a large tonnage of acid-treated bentonite used for oil refining, totaled over 10,000 tons. Destinations listed were Australia, England, Mexico, and various South American countries.

Bentonite sold or used by producers in the United States, 1940-42, by States

	. 19	940	19	1941 1942		
State	Short tons	Value	Short tons	Value	Short tons	Value
Arizona California Colorado	(1) 7, 867	(1) \$99, 840	(1) 6, 981	(1) \$69, 776	(1) 4, 745	(1) \$48, 522
Mississippi Nėvada Oklahoma	) (9)	(1)	(1)	(1)	(1)	(1)
South Dakota Texas Utah	40, 481 14, 399	274, 714 127, 949	57, 139 11, <b>59</b> 3	401, 758 105, 312	88, 149 17, 651	664, 449 127, 941 (1)
Wyoming Undistributed <sup>2</sup>	91, 714 96, 571	976, 844 440, 114	145, 574 132, 741	1, 369, 057 505, 997	139, 410 125, 012	1, 259, 863 447, 734
yargiotisyonaa aa delem diiw bad re	251, 032	1, 919, 461	354, 028	2, 451, 900	374, 967	2, 548, 509

<sup>&</sup>lt;sup>1</sup> Included under "Undistributed."

Includes States indicated by "(1)."

### FULLER'S EARTH

Shipments of fuller's earth were only 2 percent less in 1942 than in 1941, in spite of a considerably greater reduction in oil-refining activity. The mineral-oil refining industry consumed 84 percent and the vegetable-oils 10 percent of total shipments.

Although during the past 20 years fuller's earth has depended largely on the petroleum industry, it has not participated fully in that industry's expansion. As illustrated in figure 2, during the 1920's consumption of fuller's earth increased in direct proportion to petroleum output, but in the 1930's it lost ground almost continuously. The decline in use of fuller's earth was due to the increased popularity of colored fuels, to improvements in refining methods, and even more directly to the fact that it was forced to meet the competition of materials like bauxite and synthetics that have properties desirable in refining oils. Although the first cost of the competitive products is not low, their greater durability makes them economical. Activated earths have also made deep inroads into the market for natural bleaching clays.

The same active competition has carried over into catalytic petroleum cracking, which developed rapidly during the 1930's. Fuller's earth has had a somewhat varied acceptance as a catalyst, but research has developed a specially treated product that is to be used in some of the new high-octane plants.

<sup>6</sup> Information furnished by Petroleum Administration for War.

CLAYS 1325

The decline in consumption of fuller's earth was arrested in 1941 and, when compared with petroleum refining, relatively more was used in 1942. People in the industry believe that although this may have resulted from some tonnage being absorbed into plants under construction and not yet operating, it is more likely that in some refineries the pressures of wartime production have led to somewhat earlier rejection of fouled earth, thus increasing the clay used per unit of petroleum product.

Only part of the recovery in 1941 can be attributed to reclassification of borderline material and no additional reclassification took place in 1942, so the evidence indicates that the long downward

trend may have run its course.




FIGURE 2.—Mine shipments of fuller's earth compared with petroleum-refining activity (Federal Reserve Board Index), 1923-42.

Texas was the leading fuller's earth-producing State in 1942, with 42 percent of the total; the Florida-Georgia district contributed 41 and Illinois 15 percent. The average value of Texas clay, however, was only \$8.38 per ton as compared with \$8.70 for Illinois and \$13.14 for Florida-Georgia. Fuller's earth has many grades, and some have relatively rigid specifications; thus, prices usually range from \$5.50 to \$16 per ton in most areas, depending on the mesh size and degree of preparation.

In recent peacetime years imports of fuller's earth have been limited to relatively expensive materials equivalent to 1 or 2 percent of domestic production. By 1942, imports had shrunk to an insignificant 287 tons, all from the United Kingdom and valued at \$4,716 (\$16.43 per ton); in 1941, 342 tons valued at \$5,042 entered the

country.

Exports reported by producers to the Bureau of Mines were more substantial—6,052 tons valued at \$50,080 in 1942. Shipping shortages took their toll, however, as these totals are much less than the 10,722 tons valued at \$98,847 reported for 1941.

Fuller's earth sold or used by producers in the United States, 1940-42, by States

State	19	10	19	41	19	1942	
	Short tons	Value	Short tons	Value	Short tons	Value	
Florida and GeorgiaIllinois	79, 898 (1)	\$917, 365 (1)	91, 925 26, 676	\$1,075,318 209,577	83, 007 30, 421	\$1,091,062 264,611	
TexasOther States 2	34, 039 32, 631	277, 229 276, 489	77, 033 11, 812	713, 085 113, 694	85, 012 5, 804	712, 303 71, 694	
	146, 568	1, 471, 083	207, 446	2, 111, 674	204, 244	2, 139, 670	

Included under "Other States."
 1 Included under "Other States."
 1 1940: Colorado, Illinois, Nevada, New Mexico, and Tennessee; 1941: California, Nevada, New Mexico, Tennessee, and Utah; 1942: California, Colorado, Nevada, and Utah.

## MISCELLANEOUS CLAYS

This classification is simply a grouping of various clays that do not fit logically into any of the types discussed elsewhere in this chapter. As is apparent from the foregoing table of uses, the clays utilized in making common brick, sewer pipe, and other heavy-clay products constitute the major part of the tonnage, followed by much the same type of material used in cement manufacture. Third in importance are the finely divided clays that are applied alone or admixed with bentonite and other constituents to produce rotary-drilling mud. Small quantities of slip clay are also included. Owing principally to the decrease in oil-well drilling and the declining demand for heavyclay products, 16 percent less miscellaneous clay was shipped in 1942 than in 1941.

Most of these clays and shales are valued at less than \$1 per ton; but the average for the class is usually somewhat higher owing to the inclusion of drilling mud, much of which sells for around \$10 per ton,

and other high-priced specialties like slip clay.

It must be emphasized that merchant clay is only a small part of the clay and shale used in heavy-clay-products manufacture. such products are made in plants at or very near the mine. ducers canvassed by the Bureau of Mines reported that in 1942 they burned over 8,500,000 tons into clay products at the mine or pit, but additional large quantities were made into heavy-clay products at the mine or pit by firms not canvassed by the Bureau of Mines. A more complete coverage of the industry is in prospect. The Bureau of the Census reported that 16,062,000 short tons of clay were produced in 1939 by the common-clay and shale industry. Although only fragmentary information is available since that time, owing to suspension of the canvass by the Census of Manufactures, it is estimated that the quantity was about 10 percent greater in 1941. Further information on this part of the industry appears in the following section on Clay Products.

Similarly, clay marketed for cement manufacture is only a small percentage of the total clay so used. In 1942, 287,639 tons of mis-

1327CLAYS

cellaneous clay were reported sold to cement companies, but the cement industry reported to the Bureau that it used 5,181,582 tons of clay and shale in 1942, nearly all of which was mined by the cement

companies on their own properties.

As most of the miscellaneous clays are cheap and abundant throughout the world, foreign trade in them is limited to higher-priced specialties. Official Department of Commerce figures do not reveal the exact total for 1942, but it is known to be small, as exports of only a few hundred tons were reported by producers to the Bureau of Mines.

Miscellaneous clay, including slip clay 1 and shale, sold or used by producers in the United States, 1940-42, by States 2

	194	ю	19	1941 1942		
State	Short tons	Value	Short tons	Value	Short tons	Value
Alabama Arkansas California Colorado Illinois Indiana Louisiana Nebraska Ohio Pennsylvania Texas Washington Other States 4	100, 522 24, 421 127, 539 62, 803 (3) 20, 086 9, 548 10, 149 10, 496 44, 156 54, 930 65, 822 14, 807 165, 286	\$60, 583 10, 533 248, 632 64, 842 (3) 9, 750 47, 566 96, 314 5, 516 18, 788 35, 256 257, 238 11, 256 270, 466	125, 563 (*) 186, 123 79, 458 73, 468 106, 362 9, 690 (*) 11, 949 52, 468 59, 565 94, 698 (*)	\$70, 273 (3) 473, 846 83, 246 66, 408 34, 038 46, 759 (2) 5, 748 21, 760 24, 856 180, 681 (4) 394, 977	97, 169 (3) 130, 698 40, 954 60, 118 97, 390 8, 049 (3) 15, 953 17, 416 17, 478 139, 913 (3) 394, 525	\$55, 470 (3) 346, 535 45, 356 60, 463 32, 890 37, 085 (8) 13, 691 23, 176 14, 547 212, 064 (9)
	710, 515	1, 136, 740	1, 210, 168	1, 402, 592	1, 019, 663	1, 177, 474

## CLAY PRODUCTS

Although the demand for structural clay products was active during the early part of 1942, it declined with the downward trend in building activity. According to figures gathered from various sources and issued by the Statistics Division, Materials Branch, War Production Board, covering glazed and unglazed common and face brick, unglazed hollow facing tile, and unglazed structural clay tile, production of brick or brick equivalent was 25 percent less in 1942 than in 1941. group of producers has operated at far less than capacity for years and operated at only 36 percent of capacity in 1942.

Consumption of these materials was encouraged by the War Production Board for both permanent and temporary structures, because a minimum of critical materials was involved, and production has been mechanized so that of 33,000 men employed in the brick and tile industry, 28,000 were either unskilled or semiskilled. In addition, transportation can be saved as the War Production Board claims there is a clay-products plant within 100 miles of every likely building-con-

struction site in the United States.

¹ Includes slip clay as follows—1940: 4,365 tons, valued at \$29,268, from Michigan, New York, and Ohio; 1941: 5,649 tons, \$40,797, from Kentucky, Michigan, New York, Ohio, and Pennsylvania; 1942: 5,164 tons, \$41,856, from Michigan and New York.

² Does not include clay burned into clay products in integrated plants at mine or pit.

² Included under "Other States."

⁴ Includes States indicated by "(³)" above, and Connecticut, Georgia, Kansas, Kentucky (1941-42), Maryland, Massachusetts, Michigan, Minnesota, Mississippi, Missouri, Montana, Nevada (1940-41), New Jersey, New Mexico, New York, Oklahoma, Oregon (1941-42), Tennessee, Utah, and Wisconsin (1941-42).

Imports are negligible. Exports are not big factors in the industry, but appreciable tonnages are shipped as follows: 81 percent to Canada, 11 percent to South and Central America, and 8 percent to other destinations.

Data on building brick and clay tile in the United States, 1940-4212

### [Millions of brick or brick equivalent]

			1940	1941	1942
Production			6,000	6, 211	4,634
Estimated capacity Stocks—January 1 Exports		 	(3) 1, 112 36	(3) 1, 149	12, 933 1, 000
	7	 	90	91	29

<sup>&</sup>lt;sup>1</sup> Abstracted from reports issued by Statistics Division, Materials Branch, War Production Board. <sup>2</sup> Includes glazed and unglazed common and face brick, unglazed hollow facing tile, and unglazed structural clay tile. Sewer pipe and paving brick not included. <sup>3</sup> Figures not available.

## TECHNOLOGIC DEVELOPMENTS

During the past few years there has been a steadily increasing interest in the possibility of utilizing clay as a source of aluminum. Up to the present the United States has depended on high-grade bauxite, because its alumina is comparatively easily available through the Bayer process and large reserves in Surinam bolster the limited quantities known to exist in this country. By comparison, clay as a class has been a leaner and more refractory source of aluminum, and although many methods of extraction have been developed none has achieved commercial success.

Into this situation the war has injected some new considerations that are acting as a powerful stimulant. From the early days of the war it was evident that the element of airpower was to become a crucial and possibly overwhelming factor in battles of the future. As today's combat aircraft is built principally of the light metals a tremendous expansion in aluminum production has taken place, bringing with it an acute realization of the slender supplies of bauxite available within the United States. The point became even clearer as the German submarine campaign along the East coast and in the Caribbean during 1942 made delivery of Surinam bauxite more difficult and costly.

Although a large body of opinion still is doubtful of the commercial prospects of clay as an aluminum ore in the postwar period if it must meet bauxite competition on an equal basis, even the most skeptical are impelled to concede that in the interest of national security the clay processes must be developed to a point that will make the country independent of foreign ore if the need should arise in the future. As to whether this may lead to the creation of a fully developed industry or be limited to small-scale plants sufficient to prove and develop the technique, only the future can reveal. In any case, both private organizations and Government agencies are actively investigating clays. During 1942 the Bureau of Mines conducted extensive clay-drilling programs.

Naturally all groups active in this movement have tended to look first for clays containing a high available alumina content, as they

1329CLAYS

The state of the s

The state of the s

offer the most immediate promise of success. The fire clays of Missouri are most attractive from that standpoint, but they are not sufficiently extensive. The high-alumina clays of Pennsylvania have the advantage of location near high-calcium limestone and coal that would be required if they were to be treated by the lime-soda process. Lower-quality clays, however, are also receiving attention, for they

are much more abundant and widely distributed.

At the request of the War Production Board, a committee of the National Academy of Sciences surveyed domestic aluminum sources, and their findings were embodied in a report submitted June 9, 1942.7 Their investigations led the committee to conclude that although bauxite was the best raw material for producing aluminum, the clays, red muds, and alunite should not be neglected. They found that the acid-process pilot plant operated by the Tennessee Valley Authority was not producing alumina pure enough to be used in the manufacture of aluminum, but they did encourage further progress by offering suggestions as to methods of purification. The following are selected quotations from the report pertaining to clay:

As a matter of insurance in the production of alumina, the War Production Board should consider the construction of lime-soda sintering plants in connection with the Bayer process plants. This would enable each Bayer process plant in the United States to operate on high-silica bauxite and it would also make possible the production of a portion of the alumina, in these combination plants,

The Committee considers a modified Pedersen process for the production of alumina from clay as the most promising process that will be independent of the Bayer process. This process consists essentially of sintering clay with lime and subsequently leaching with soda. There are many ramifications in the details and in the treatment of the liquors which need test plant study. It is therefore recommended, that the War Production Board allocate to the War Metallurgy Committee a maximum of \$100,000 for the construction and operation of a test

committee a maximum of \$100,000 for the construction and operation of \$200 tests to study the modified Pedersen process for the production of alumina from clay. It is suggested also that the War Production Board facilitate the acquisition of equipment for this test plant. A "Project Priority" is suggested.

It is recommended, that the Aluminum Co. of America be asked to prosecute vigorously pilot plant work on the lime-soda treatment of clay. To facilitate this work, it is suggested that the War Production Board assist the Aluminum Co. of America in what is production assist the Aluminum Co. of America is suggested that the War Production Board assist the Aluminum Co. of America is publication without plant acquirement for work on clay or

Co. of America in obtaining either pilot plant equipment for work on clay or, preferably, a larger pilot plant for the treatment of red mud, thus making available the present pilot plant for work on clay.

It is recommended, that the work now in progress on alumina at the College Park Experiment Station of the Bureau of Mines be continued, and that the War Production Board assist the Bureau in obtaining equipment for this work. A "Project Priority" for this alumina work is suggested.

It is suggested that large quantities of baryite could be conserved by restricting

It is suggested that large quantities of bauxite could be conserved by restricting its use in the manufacture of aluminum sulfate. Calcined kaolin clay apparently can be substituted for the production of aluminum sulfate.

As a means of acquiring a fundamental understanding of the physical structures of the various clays the X-ray and electron microscope are powerful research tools. The progress of the past 15 years is summarized in a report by Grim.<sup>8</sup> Although the electron microscope is still too new to have developed a large body of information on the clays, micrographs have shown that: 9

The montmorillonites show structures ranging from a fluffy amorphous-appearing material to well-defined, extremely thin plates. Nontronite has flat, frayed

Advisory Committee on Metals and Minerals (Zay Jeffries, chairman), National Academy of Sciences, Alumina from Domestic Sources.

Grim, Ralph E., Modern Concepts of Clay Materials: Jour. Geol., vol. 50, No. 3, April–May 1942, pp.

<sup>225-275.</sup>Shaw, B. T., and Humbert, R. P., Electron Micrographs of Clay Minerals: Proc., Soil Science Soc. America, vol. 6, 1941, pp. 146-149.

fibers; kaolinite and dickite both have hexagonal plate-shaped crystals, and halloysite has long split rods. Dickite crystals are much thicker than most kaolinitic crystals.

With a view to suggesting a series of the more important tests recognized by the various industries, whereby any given clay can be classified according to its possible uses, a group in the Bureau of Mines working under the supervision of Oliver C. Ralston prepared a syllabus of clay testing that should prove to be very useful.<sup>10</sup>

<sup>&</sup>lt;sup>10</sup> Klinefelter, Theron A., O'Meara, Robert G., Gottlieb, Sidney, and Truesdell, Glenn C., Syllabus of Clay Testing, part I, Bureau of Mines Bull. 451, 1943, 35 pp.

# **ABRASIVE MATERIALS**

By ROBERT W. METCALF

### SUMMARY OUTLINE

	Page		Page
General conditions	1331	Natural silicate abrasives	1339
Salient statistics	1331	Pumice and pumicite	1339
Natural silica abrasives	1332	Garnet	1341
Diatomite	1332	Natural alumina abrasives	1342
Tripoli	1333	Corundum	1342
Quartz	1334	Emery	1342
Ground sand and sandstone	1335	Natural carbon abrasives	1342
Abrasive sands	1336	Abrasive or industrial diamonds	1342
Special silica-stone products	1336	Artificial abrasives	1345
Grindstones and pulpstones	1336	Miscellaneous mineral abrasive materials	1347
Oilstones and related products	1337	Foreign trade	1347
Millstones	1338		-DI.
Grinding nebbles and tube-mill liners	1338		

## GENERAL CONDITIONS

The total value of the products of the natural abrasives industries rose about 9 percent in 1942 compared with 1941. All classes of abrasives shown except tripoli, millstones, garnet, and grindstones made sizable gains in value of products. The value of sales of quartz and of ground sand and sandstone was at a high level; in fact, the value of ground sand and sandstone exact the highest record. The value of pumice and pumicite sales also was the highest yet recorded. The sales value of tube-mill liners and grinding pebbles in 1942 increased moderately over 1941.

Salient statistics of the abrasives industries in the United States, 1941-42

	1941	1942	Percent of change in 1942
Domestic production (sold or used by producers):			
Natural silica abrasives:			. v 1
Diatomite	(1)	(1)	
1T1D0H	\$421,746	\$272,428	-38
Quartz	228, 587	331, 494	+45 +19
Ground sand and sandstone	3, 073, 730	3, 646, 643	+19
Special silica-stone products:			
Grindstones and pulpstones		539, 739	-1
Oilstones and related products		(1)	
Millstones		10, 391	-33 +7
Flint lining and grinding pebbles	276, 042	295, 761	+7
Natural silicate abrasives:			1 N.
Pumice and pumicite	669, 514	706, 199	+5 -19
Carret	371,752	299, 904	-19
Natural alumina abrasives:			. 5
Emery	42, 484	49, 413	+16
Motol motomal absorbure 0	A 7 044 000	44 454 450	• • • •
Total natural abrasives 2	3 5, 644, 990	2 6, 151, 972	2- <b>1</b> -9
Total artificial abrasives 3	16, 444, 319	23, 856, 488	+45
oreign trade:	15 450 146	00 000 000	
	15, 470, 148	22, 696, 338	+47
Exports	3, 219, 642	6, 684, 352	+108

Bureau of Mines not at liberty to publish figures. Average for diatomite for 1939-41 was \$1,915,405.
 Excludes value of diatomite and oilstones and related products, which the Bureau of Mines is not at liberty to publish.
 Includes material produced in Canada; Bureau of Mines not at liberty to publish United States data

Paced by the enormously increased demand for abrasives caused by the war, the production of crude manufactured (artificial) abrasives surpassed all previous records by substantial margins for the third successive year. The combined total output reached by aluminum oxide, silicon carbide, and metallic abrasives in 1942 rose to 370,578 short tons valued at \$23,856,488, 33 percent more in tonnage and 45 percent more in value than the figures reported for the former record year (1941). With aluminum oxide and silicon carbide production operating at full capacity and metallic abrasives production at nearly 75 percent of capacity, all three classes of manufactured abrasives for which data are shown achieved record outputs in both quantity and value. The percentages of increase in tonnage in 1942 compared with 1941 were: Silicon carbide, 37 percent; aluminum oxide, 24 percent; and metallic abrasives (steel shot and grit), 45

percent.

The total value of imports of natural abrasive materials into the United States rose to \$22,696,338 in 1942, 47 percent greater than in 1941, when the total value reached \$15,470,148. In both 1941 and 1942, imports of smaller diamonds ("glaziers' and engravers', unset, and miners' ") into the United States continued at a record-breaking rate, increasing to 6,882,248 carats in 1941 and 11,203,704 carats in 1942, compared with 3,809,071 carats in 1940. Imports of bort in 1942 rose sharply compared with 1941 and were the highest reported since 1937. Imports of corundum ore, which doubled in quantity from 1940 to 1941, declined somewhat in 1942. As in 1941, there were no receipts of emery ore, and pumice imports were very small. combined value of exports of domestic abrasives and abrasive products in 1942 was twice that in 1941 and higher than in any year since 1920. A very large increase compared with 1941 in the export value of emery and corundum abrasive wheels brought the 1942 total of these products almost to the 1918 figure of \$3,862,531. The value of exports of grindstones rose 20 percent, whereas the value of all other natural abrasives, whetstones, hones, etc., dropped slightly.

This chapter includes data for most of the materials used chiefly as abrasives, although certain clays, oxides, and substances mentioned later under "Miscellaneous mineral abrasive materials" are not included in the statistics presented herein. On the other hand, certain of the "abrasive materials" for which figures are included also have

important nonabrasive uses.

### NATURAL SILICA ABRASIVES

Diatomite.—The Bureau of Mines has not been at liberty to publish annual production data for diatomite since 1926. Total output (sales) for 3-year periods, however, may be shown. Total sales for the three most recent of such periods were as follows—1939-41: 360,502 short tons valued at \$5,746,216; 1936-38: 279,645 tons valued at \$4,377,353; and 1933-35: 244,342 tons valued at \$3,618,428. Sales of diatomite in 1942 were somewhat higher in quantity and value than for 1941.

As in other recent years, California and Oregon were the chief producing States. Other States in which diatomite was produced in

1942 were Florida, Idaho, Nevada, and Washington.

About half of the diatomaceous earth marketed in the United States in 1942 was used in filtration, about one-quarter in various types of insulation, another one-sixth as fillers or admixtures, and the remainder for other miscellaneous uses, including small amounts for abrasives.

Prices at the beginning of 1942, according to E&MJ Metal and Mineral Markets, were as follows: Crude dried diatomite f. o. b. mines (Nevada), in bulk, \$7, in bags, \$12; 40-mesh, \$18; 200-mesh, \$22.50; low-temperature insulation, \$19; and high-temperature, \$40. On April 30 and throughout the year, quotations were: Crude dried diatomite f. o. b. mines (Nevada), in bulk, \$7 (nominal); 98-100 mesh, \$20; low-temperature insulation, \$19; high-temperature insulation, \$30; fine abrasives, 2 cents a pound (all bags are extra).

Several applications of diatomite were reported in the literature. Its employment as a decolorizing filter aid,1 the advantages of its use as an ingredient of paint,2 and in the manufacture of paper,3 and its utilization in the construction of small homes 4 were described.

A flow sheet giving a simplified description of the mining and processing of diatomite at the operations of the Johns-Manville Products Corporation, Lompoc, Calif., accompanied by photographs of mines and refining plants, was published. Japanese deposits of diatomite and their uses were described during 1942.6

Tripoli.—Both the quantity and value of tripoli (including Pennsylvania rottenstone) dropped sharply to 17,536 tons, worth \$272,428, the lowest point in tonnage since 1932. This decline was due largely to the lack of output reported in 1942 for Oklahoma and Texas. Production in 1942 was obtained from Arkansas, Illinois, Missouri, and Pennsylvania (rottenstone).

Tripoli (including Pennsylvania rottenstone) sold or used by producers in the United States, 1938-42

Year	Illin	ois	Other States 1 Total				
	Year	Short tons	Value	Short tons	Value	Short tons	Value
1938 1939 1940 1941 1942		8, 141 11, 134 11, 521 13, 833 12, 575	\$117, 107 148, 310 155, 576 200, 700 203, 390	14, 047 22, 340 18, 691 15, 468 4, 961	\$211, 974 318, 070 210, 993 221, 046 69, 038	22, 188 33, 474 30, 212 29, 301 17, 536	\$329, 081 466, 380 366, 569 421, 746 272, 428

<sup>&</sup>lt;sup>1</sup> 1938: Arkansas, California, Missouri, Oklahoma, Pennsylvania, and Tennessee; 1939: Arkansas, California, Missouri, Oklahoma, Pennsylvania, Tennessee, and Texas; 1940-41: Arkansas, California, Missouri, Oklahoma, Pennsylvania, and Texas; 1942: Arkansas, Missouri, and Pennsylvania.

<sup>1</sup> Boyd, R., and Schmidt, R. W., Decolorizing Filter Aids, Kyrite and Dicalite M-23: Ind. and Eng. Chem., ind. ed., vol. 34, No. 6, June 1942, pp. 744-748.

2 Hall, H. W., Diatomacous Silica and Its Application in the Paint Industry: Paint, Oil and Chem. Rev., vol. 104, No. 7, March 26, 1942, pp. 12, 14, 16, 18.

3 Hall, H. W., Diatoms in Paper Manufacture: Paper Trade Jour., vol. 115, No. 14, October 1, 1942, pp. 127, 190.

<sup>107-109</sup> 

 <sup>10/-109.
 4</sup> Architectural Forum, Diatalum Dwellings: Vol. 77, No. 3, September 1942, pp. 108-111.
 5 Chemical and Metallurgical Engineering, Mining and Refining of Diatomite—Flow Sheet: Vol. 49,
 No. 8, August 1942, pp. 110-113.
 6 Kawasima, T., and Siraki, Y., Japanese Diatomaceous Earths and Their Industrial Application (abst);
 Jour. Am. Ceram. Soc., vol. 25 (Ceram. Abs., vol. 21), April 1, 1942, pp. 89-90.

Tripoli (including Pennsylvania rottenstone) sold or used by producers in the United States, 1940-42, by uses

	19	<b>£</b> 0	19	11	1942		
Use	Short tons	Value	Short tons	Value	Short tons	Value	
Abrasives	10, 279 1, 683 8, 451 1, 840 7, 959	\$119,609 15,895 113,862 16,949 100,254	13, 407 1, 179 10, 020 1, 925 2, 770	\$198, 252 15, 168 145, 063 22, 835 40, 428	5, 447 754 8, 887 (1) 2, 448	\$85, 013 8, 895 144, 055 (1) 34, 465	
	30, 212	366, 569	29, 301	421, 746	17, 536	272, 428	

Included under "Other uses."
 1940: Filter block, foundry facing, and unspecified; 1941: Foundry facing and unspecified; 1942: Foundry facing, drilling mud, and unspecified.

Fillers and abrasives continued to be the largest markets for tripoli in 1942, as in 1941, absorbing 51 and 31 percent of the total sold. Other uses in 1942 were concrete admixture, oil-well drilling, foundry

facing, and uses not specified.

Quotations on tripoli, as reported by E&MJ Metal and Mineral Markets, remained unchanged during 1942, as follows (prices per ton, f. o. b. Missouri, in paper-lined burlap bags, minimum carload, 30 tons): Once-ground through 40-mesh, rose or cream colored, \$14.50; double-ground through 110-mesh, rose or cream, \$16; air-floated through 200-mesh, \$26.

Quartz.—The output of crude, crushed, and ground quartz from pegmatite veins or dikes and from quartzite in 1942 rose to 65,878 short tons worth \$331,494, a gain of 58 percent in quantity and 45 percent in value compared with 1941. This was the largest tonnage reported since 1918 and the highest value since 1914. Sales of ground quartz in 1942 more than doubled compared with 1941, and sales of crushed material were 90 percent more than in 1941, but quartz sold or used without preparation decreased sharply.

Quartz (crude, crushed, and ground) 1 sold or used by producers in the United States, 1938-42

	Crude		Crushed		Ground		То	Value		
Year	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value		
1938. 1939. 1940. 1941. 1942.	4, 493 13, 739 3, 606 8, 977 2, 043	\$17, 023 *45, 785 17, 099 39, 247 7, 937	9, 930 15, 504 17, 652 24, 101 45, 747	\$27, 941 49, 186 58, 897 94, 913 144, 808	4, 188 5, 716 10, 607 8, 607 18, 088	\$43, 233 58, 067 100, 394 94, 427 178, 749	18, 611 34, 959 31, 865 41, 685 65, 878	\$88, 19 153, 03 176, 39 228, 58 331, 49		

<sup>1</sup> To avoid duplication, the ground material shown here is only that ground by the original producers of the crude quartz or by grinders who purchase from small miners not reporting their production.

In 1942, output of quartz was reported from 15 States, the same number that produced in 1941; however, no output was reported from Oregon in 1942 and none from Virginia in 1941.

Quartz (crude, crushed, and ground) 1 sold or used by producers in the United States. 1940-42, by States

State	19	40	19	41	1942		
State	Short tons	Value	Short tons	Value	Short tons	Value	
Arizona California Oregon	} 2,141 1,600	\$25, 548 10, 000	3, 974	\$50, 243	{ (2) (2) (2)	(2) (2)	
Maine Massachusetts New Jersey	160 786	538 4, 716	202 850	722 5, 525	364 1,029	\$922 8, 137	
Pennsylvania Ohio	(2) (2)	(2)	778	7, 181	975	8, 649	
North Carolina Virginia	3,842	25, 063	(2)	(²)	(2) (2)	(2) (2)	
TexasOther States 3	23, 336	110, 525	1, 485 34, 396	14, 345 150, 571	319 63, 191	3, 190 310, 596	
	31,865	176, 390	41,685	228, 587	65, 878	331, 494	

To avoid duplication, the ground material included is only that ground by the original producers of the crude quartz or by grinders who purchase from small miners not reporting their production.
 Included under "Other States."
 1940: Maryland, New Jersey, New York, Pennsylvania, Tennessee, and Wisconsin; 1941: Maryland, New Hampshire, New York, North Carolina, Tennessee, and Wisconsin; 1942: Arizona, California, Maryland, New York, North Carolina, Tennessee, Virginia, Washington, and Wisconsin.

The production and grinding of "flint"—apparently sugar quartz or vein quartz—by the United Feldspar & Minerals Corporation, Spruce Pine, N. C., for use in sandpaper and abrasives was described. Deposits of quartz and quartzite suitable for commercial development in New Hampshire were described and analyses of quartzites given by Mévers.8

Ground sand and sandstone.—Sales of ground sand and sandstone in 1942 rose to 527,886 short tons, only 1 percent less than the record year (1917—532,454 tons) and 8 percent greater than in 1941. The value of sales, however, reached \$3,646,643, 205 percent more than in 1917 and 19 percent higher than the former record reported in 1941. Output in all States or groups of States for which comparative totals are shown was substantially higher in 1942 than in 1941, except for Ohio Virginia West Virginia in which production (calca) and all shelds. Ohio-Virginia-West Virginia, in which production (sales) only slightly exceeded that for 1941. States producing sizable tonnages of ground material were Illinois, New Jersey, Ohio, and Pennsylvania.

## Ground sand and sandstone sold or used by producers in the United States, 1938-42

Year	Short tons	Value	Year	Short tons	V.alue
1938	237, 167	\$1, 425, 445	1941	487.665	\$3, 073, 730
1939	310, 512	1, 930, 301	1942	487, 665 527, 886	3, 646, 643
1940	342, 218	2, 088, 314			5 31,54

<sup>7</sup> Engineering and Mining Journal, "Flint" Ground for Abrasives: Vol. 143, No. 11, November 1942, p. 55,
 <sup>8</sup> Meyers, T. R., Some New Hampshire Quartz Deposits: New Hampshire State Planning Deveopment Commission Mineral Resources Survey VI; Chem. Abs., vol. 37, No. 6, March 20, 1943, p. 1353.

Ground sand and sandstone sold or used by producers in the United States, 1940-42, by States

	1	1940 19			1942		
State	Short tons	Value	Short tons	Value	Short tons	Value	
California	5, 505	\$39, 080	(1)	(1)	8, 371	\$68, 324	
Washington Illinois Massachusetts New Jersey and Pennsylvania	106, 397 1, 425 122, 304	628, 488 6, 240 641, 021	131, 581 1, 352 174, 305	\$808, 402 6, 327 954, 929	158, 853 2, 761 188, 598	1, 087, 481 13, 948 1, 143, 746	
Ohio, Virginia, and West Virginia Other States	96, 133 10, 454	688, 321 85, 164	149, 542 30, 885	1, 092, 784 211, 288	149, 625 19, 678	1, 167, 207 165, 937	
	342, 218	2, 088, 314	487, 665	3, 073, 730	527, 886	3, 646, 643	

<sup>&</sup>lt;sup>1</sup> Included under "Other States." <sup>1</sup> 1940: Missouri, North Carolina, and Wisconsin; 1941: California, Missouri, and Wisconsin; 1942: Georgia, Missouri, and Wisconsin.

The three chief uses for ground sand and sandstone in 1942 were foundries (34 percent of the total); pottery, porcelain, and tile (26 percent); and abrasives (22 percent). Other important outlets are for fillers and in the glass and enamel trades.

Ground sand and sandstone sold or used by producers in the United States in 1942, by uses

ing a filipating of the second					Va	lue
	Use			Short tons	Total	Average per ton
		<del></del>				*****
Abrasive:	scouring compound			87, 317	\$507, 669	\$5.8
Other	scouring compount		 	28, 106	200, 905	7.1
Enamel			 	22, 043	141, 305	6.4
Filler			 	25, 419	190, 852	7. 5
Foundry			 	177, 269	1, 179, 327	6.6
Glass			 	15, 959	110, 114	6. 90 7. 93
Pottery, porcelain	and tile		 	138, 995	1, 100, 185 216, 286	6.60
Other uses			 	32, 778	210, 280	0.0
	A STORY OF THE STORY			527, 886	3, 646, 643	6.9

Abrasive sands.—Production of natural sands with a high silica content, employed for sand blasting, scouring stone, grinding glass, sand paper, and other abrasive uses, rose in 1941—the latest year for which data are at present available—to 1,001,814 short tons valued at \$1,388,966, compared with 856,309 tons valued at \$915,925 in 1940, an increase of 17 percent in tonnage and 52 percent in value. The 1941 total includes 371,049 tons of blast sand valued at \$912,626—45 percent more in quantity and 53 percent more in value than that reported in 1940. See chapter on Sand and Gravel for 1942 figures.

## SPECIAL SILICA-STONE PRODUCTS

Grindstones and pulpstones.—Total sales of pulpstones and grindstones in 1942 totaled 14,681 short tons valued at \$539,739, a decrease of 6 percent in tonnage and a slight decrease in value compared with 1941. In spite of heavy competition from manufactured stones, the tonnage of grindstones sold in 1942 was but 6 percent less than in 1941, and the value only slightly less than in 1941 although considerably above that in 1940. Output of natural pulpstones in 1942 decreased about 2 percent in tonnage to 1,918 tons, although the value rose 5 percent to \$116,976. Grindstones were quarried in 1942 in Ohio and West Virginia and pulpstones in Washington and West Virginia.

Grindstones and pulpstones sold by producers in the United States, 1938-42

				Pulpstones	
Year	Grind	stones	Qua		
	Short tons	Value	Pieces	Equivalent short tons	Value
1938	4, 653 7, 917 8, 790 13, 573 12, 763	\$149, 019 257, 350 284, 809 434, 208 422, 763	417 672 901 685 528	1, 553 2, 517 4, 533 1, 963 1, 918	\$90, 987 169, 025 211, 639 111, 348 116, 976

The production of grindstones by the Constitution Stone Co., Constitution, Ohio, in its quarries and finishing mills in Ohio and West Virginia was described by Random. The circular, rough blocks of stone coming from the quarry weigh up to 5 or 6 tons and may measure 7 feet in diameter, but grindstones completed at the company finishing mills range from 6 to 84 inches in diameter and from 1 to 20 inches in thickness. The stones produced are a medium-coarse, hard grit and are shipped largely to manufacturers of saws, millworking equipment, machine knives, and similar products. Although competition from artificial stones has been severe in recent years, the war has aided in maintaining a fairly active market for the natural product.

The development of pulpstones during the present century was traced by Dupuis. Different patterns of the working face of sand-stone and artificial pulpstones were illustrated in a paper-trade journal 11 to suggest methods of obtaining increased grinding surfaces. Characteristics and structure of foreign (Finnish) artificial pulpstones

were discussed.12

Oilstones and related products.—Sales of natural sharpening stones, including oilstones, whetstones, scythestones, and rubbing stones, were somewhat higher in 1942 than in 1941. The Bureau of Mines, however, is not at liberty to publish the figures. States in which production was made in 1942 and the type of stone reported from each were as follows: Arkansas, oilstones and whetstones; Indiana, scythestones, whetstones, and rubbing stones; New Hampshire, scythestones; and Ohio, scythestones, whetstones, and lathestones.

556250—43——85

Random, Bill, Grindstones Come Back: Compressed Air Mag., vol. 47, No. 9, September 1942, pp. 6837-6840.

Dupuis, D. E., Forty Years Progress in Pulpstones and Burrs: Pulp and Paper of Canada, vol. 43, No. 8, July 1942, pp. 578-581.

11 Paper Industry and Paper World, Case Studies of Various Pulpstone Dressings: Vol. 24, No. 7, October 1942, pp. 702-703.

12 Pellinen, H., Pulpstone Structure: Finnish Timber Jour., vol. 23, No. 10, May 31, 1941, p. 192; through Bull. Inst. Paper Chem., vol. 12, 1942, p. 224; abs. Paper Ind. and Paper World, vol. 24, No. 1, April 1942,

Oilstones, whetstones, scythestones, and other sharpening stones sold by producers in the United States, 1938-42

Year	Short tons	Value	Year	Short tons	Value
1938	511	\$130, 277	1941	(1)	(I)
1939 1940	(1) 620	115, 805	1942	(i)	(1)
			to the second of		

<sup>1</sup> Bureau of Mines not at liberty to publish figures.

Millstones.—The value of millstones in 1942 decreased to \$10,391—33 percent less than in 1941 and 6 percent less than in 1939. In 1942 millstones were produced in Ulster County, N. Y.; Rowan County N. C.; and Montgomery County, Va. Output of chasers also was reported from New York State.

Value of millstones, chasers, and dragstones sold by producers in the United States, 1938-42

	New	York	Other	States 1	Total	
Year	Producers	Value	Producers	Value	Producers	Value
1938 1939 1940 1944 1942	4 6 3 5 2	(2) \$2, 584 (2) 3, 558 (2)	2 3 2 3 3 3	(2) \$8; 500 (2) 12, 021 (2)	6 9 5 8 5	\$3,743 11,084 6,558 15,579 10,391

<sup>&</sup>lt;sup>1</sup> 1938: Virginia; 1939-40 and 1942: North Carolina and Virginia; 1941: North Carolina, Virginia, and West Virginia.

<sup>2</sup> Bureau of Mines not at liberty to publish figures.

Grinding pebbles and tube-mill liners.—Total sales of grinding pebbles and tube-mill liners in 1942 increased to 18,063 short tons valued at \$295,761, a gain of 6 percent in tonnage and 7 percent in value compared with 1941. Of the total for 1942, grinding pebbles totaled 15,487 tons worth \$245,794 and tube-mill liners 2,576 tons valued at \$49,967. Similar figures for 1941 were: Grinding pebbles, 13,561 tons, \$221,826; tube-mill liners, 3,411 tons, \$54,216.

In 1942, grinding pebbles or tube-mill liners, or both, were produced in six States—Alabama, California, Minnesota, North Carolina, Texas, and Wisconsin. In Alabama, the Great Lakes Foundry Sand Co., Detroit, Mich., marketed grinding pebbles produced near Elmore. John C. Momand, Carlsbad, Calif., sold small quantities of beach pebbles.

Jasper Stone Co., Sioux City, Iowa, in 1942 continued production and sales of both liners and mechanically rounded pebbles from its Jasper (Minn.) quartzite deposits. The Southern Products & Silica Co., Lilesville, N. C., owned by Charlotte Chemical Laboratories Inc., Charlotte, N. C., and the W. R. Bonsal Co., Hamlet, N. C., produced silica pebbles near Lilesville, N. C. This firm also marketed flint pebbles produced in Texas. Harris Granite Quarries Co., Salisbury, N. C., produced rounded granite cubes and granite liners.

True flint pebbles were shipped from various points in four counties in south central Texas by Philip S. Hoyt, Van Horn, Tex. The Arlcy Mining Co., Pearsall, Tex., owned by the Richard L. Cawood Co., East Liverpool, Ohio, produced flint pebbles, as did also the

Dezendorf Marble Co., Austin, Tex. The Baraboo Quartzite Co.,

Baraboo, Wis., marketed quartzite pebbles and liners.

Genuine nodular amorphous flint pebbles, of good shape and said to have similar wearing qualities, purity, and the appearance and color of French pebbles, are being marketed by the Richard L. Cawood Co., East Liverpool, Ohio, according to the trade press. 13 The pebbles occur in the so-called Edwards chalk in south central Texas in beds of a red claylike matrix. Some of this matrix remains attached to the pebbles as a thin coating which, for certain uses, must be removed by ball milling. All pebbles, however, are not of equal quality, and many must be discarded.

Grinding mediums and mill liners made of Salisbury granite, quarried near Salisbury, Rowan County, N. C., were described.<sup>14</sup> Sizes of liners and pebbles, with recently quoted prices for each size and degree of preparation, are given. A domestic burrstone lining material has been developed, after careful tests, to replace the producformerly imported from Belgium. The new-type burrstone differs in structure from the Belgian product, does not have soft spots, and

withstands impact and abrasion tests satisfactorily.15

Quartzite pebbles are abundant in certain areas of southwestern Saskatchewan, according to the Department of Natural Resources of the Province. A reconnaissance survey of three areas in the Province has disclosed large supplies. 16 Careful hand sorting would be necessary, as other rocks of similar size, shape, and color occur with the Tests to determine their suitability for use as grinding mediums have been undertaken.

## NATURAL SILICATE ABRASIVES

Pumice and pumicite.—Sales of pumice and pumicite in 1942 topped those in the previous record year (1941) by 8 percent in tonnage and 5 percent in value, rising to 126,522 short tons valued at \$706,199, compared with 117,310 tons worth \$669,514 in 1941.

Output of pumice or pumicite in 1942 was reported from seven States—California, Kansas, Nebraska, New Mexico, Oklahoma, Oregon, and Texas. The leading producing States in 1942 were

California, Kansas, New Mexico, and Nebraska.

Pumice and pumicite sold or used by producers in the United States, 1938-42

Year	Short tons	Value	Year	Short tons	Value
1938 1939 1940	65, 742 89, 159 82, 407	\$312, 886 424, 780 449, 914	1941 1942	117, 310 126, 522	\$669, 514 706, 199

Pumice and pumicite used for abrasive purposes increased 11 percent in 1942 over 1941. Sales or use in concrete admixture and aggregate continued at a high level. Consumption for acoustic

<sup>13</sup> Pit and Quarry, vol. 35, No. 1, July 1942, p. 124; Chem. and Met. Eng., vol. 49, No. 7, July 1942, p. 134; Ceram. Ind., vol. 39, No. 4, October 1942, pp. 39-40.

14 Engineering and Mining Journal, Grinding Media from Salisbury Granite: Vol. 143, No. 11, November 1942, p. 61.

15 Grindings and Mixings, Two-Year Test Proves Superiority of Domestic Burrstone Linings: March 1943, p. 1; pub. by Paul O. Abbe, Little Falls, N. J.

16 Engineering and Mining Journal, Quartz Pebbles for Ball-Mill Grinding in Saskatchewan: Vol. 144, No. 4, April 1943, p. 71; Canadian Min. and Met. Bull., No. 372, April 1943, p. 137.

plaster decreased 7 percent in tonnage, although showing a substantial increase in value. The decline in quantity sold or used for acoustic purposes and for concrete may be more apparent than real, however, since two or three firms producing moderate-size tonnages did not report their figures broken down by uses. In the absence of information by means of which estimates as to possible uses might be made, the amounts in question necessarily were placed under "Other uses."

Pumice and pumicite sold or used by producers in the United States, 1940-42, by uses

		940	19	941	1942	
Use	Short tons	Value	Short tons	Value	Short tons	Value
Abrasive: Cleansing and scouring compounds and hand soaps Other abrasive uses. Acoustic plaster Concrete admixture and concrete aggregate	49, 359 836 3, 712 22, 045	\$234, 768 7, 563 67, 906 48, 204	36, 246 12, 785 4, 885 56, 159	\$265, 361 127, 003 78, 538 72, 242	50, 324 4, 084 4, 552 46, 163	\$353, 788 90, 286 121, 551 57, 219
Other uses 1	6, 455 82, 407	91, 473	7, 235	126, 370 669, 514	126, 522	83, 355 706, 199

<sup>1940:</sup> Asphalt, heat or cold insulation, insecticide, stucco, lime mortar, and unspecified uses; 1941: Asphalt, insulating mediums, insecticide, paint products, and unspecified; 1942: Asphalt, insulation, insecticide, paint products, filtration, and unspecified.




FIGURE 1.—Trends, by uses, of pumice and pumicite sold or used by producers in the United States, 1933-42.

いことがはいいとうないというできないます。

TOTAL OF THE PARTY OF STREET

THE PARTY OF THE P

Although volcanic ash is cheap and widely distributed in certain areas, its iron content has greatly restricted its use in ceramic applications.17 Attempts to remove the iron by various means, including concentration, magnetic separation, and leaching, have been unsuccessful, as the iron is in the form of a complex silicate. Decolorizers, such as selenium and selenium combined with arsenic trioxide, gave promising results. The plasticity, dry strength, and glaze fit of hotel chinaware bodies are improved by substituting substantial quantities of volcanic ash for ball clay and feldspar. Potential applications are the use of volcanic ash as a glaze component and in low-cost glass. Iron oxide, however, usually gives a yellow or ivory tint to the fired ware.

The manufacture of a fire-resistant concrete masonry unit using pumice is described in the trade press. 18 Volcanic ash deposits in Texas, in Grimes County, 19 in Polk and adjoining counties, 20 and in the Rio Grande area, 21 were described. In the last-named study, the chemical and physical compositions of volcanic ash in that area were analyzed. When mixed with plastic clays, the resulting brick is said to be far superior to ordinary brick.

Garnet.—Although sales of garnet reported to the Bureau of Mines in 1942 decreased 21 percent in quantity and 19 percent in value, they were still somewhat above the levels of 1939, and the period 1931 to 1936. (See fig. 2.) The output of garnet produced for sale in 1942




FIGURE 2.—Marketed production of abrasive garnet and domestic emery in the United States, 1920-42.

came from New York, North Carolina, and Idaho. Mas-Celo Mines, Inc., Burnsville, N. C., ceased business in June 1942, and the property remained idle the rest of the year. Yancey Cyanite Co. was to reopen the plant early in 1943. Recovery of garnet concentrates of probable

American Ceramic Society, American Ceramic Society Committee on Research Reports on Enamel, Glass, Refractories, Ceramics (Structural), Whiteware, Materials: Bull., vol. 21, No. 6, June 1942, pp. 92-101 (see esp. p. 99).
 Enhart, Walter B., Making a Porous Concrete Pipe: Rock Products, vol. 45, No. 4, April 1942, pp.

<sup>10</sup> Lanhart, Walter B., Making a Porous Concrete Pipe: Rock Products, vol. 40, No. 4, April 1922, pp. 64-66.
10 Ramsay, George D., Report on Volcanic Ash, Building Stone, and Gravel Deposits of Grimes County as a Part of the Mineral Resource Survey of Grimes County: Univ. of Texas, Bureau of Econ. Geol., Min. Res. Survey No. 14, 1936, 7 pp.
10 Shafer, George H., Rice Sands in Polk and Adjoining Counties, with Notes on Volcanic Ash and Bentonitic Clays: Univ. of Texas, Bureau of Econ. Geol., Min. Res. Survey 41, 1942, 5 pp.
11 Ryan, J. J., Field Findings on Rio Grande Volcanic Ash: Paper presented before Ceramic Society of the Southwest, at Univ. of Texas, October 17, 1942; reported in abs. in Brick and Clay Record, vol. 101, No. 5, November 1942, p. 8.

commercial value from Oregon beach sands was reported by Dasher, Fraas, and Gabriel.<sup>22</sup>

		producers		

-	Year	Short tons	Value,	Year	Short tons	Value
19	38	2, 669	\$191, 658	1941	5, 501	\$371, 752
19	3940	4, 056 4, 716	278, 534 259, 345	1942	4, 357	299, 904
10		7,110	200, 010	<ul> <li>Table With the section in</li> </ul>	100	

Garnet prices, as quoted by E&MJ Metal and Mineral Markets. remained constant during 1942, as follows: New Hampshire, f. o. b. mines, per ton, concentrate, \$35; grain, \$80 to \$140; New York Adirondack garnet concentrates, grain, \$85; Spanish grades, c. i. f. port of entry, \$70 (nominal).

### NATURAL ALUMINA ABRASIVES

Corundum.—Practically all of the natural corundum used in this country in recent years has been imported from South Africa, although small receipts from other countries have been reported occasionally. The need of using it for war purposes and the uncertainties of a long ocean haul have led to intensive investigation of known or potential deposits, in order to develop domestic sources of supply if possible. In North Carolina a survey of old producing localities and existing reserves was undertaken at the request of the War Production Board.23 Deposits in other regions also have been studied.

Emery.—The sales of emery produced in the United States in 1942 rose to 5,277 short tons worth \$49,413, an increase of 8 percent in tonnage and 16 percent in value compared with 1941 (see fig. 2). This figure is the highest since 1918, when output (including a small amount of corundum) totaled 10,422 tons. The entire output in 1942 came from the Peekskill (N. Y.) region. Producers reporting shipments were Joe DeLuca, Di Rubbo & Ellis, and Scalzo & Pisano. Floors surfaced with a top coating of graded emery aggregate, portland cement, and water are rendered nonslippery, even when wet, give good traction, and have increased load-bearing properties and high resistance to wear.24

Emery sold or used by producers in the United States, 1938-42

Year	Short tons	Value	Year	Short tons	Value
1938			1941	4, 876	\$42, 484 49, 413
1939 1940	765 1, 046	\$6, 828 9, 349	1942	5, 277	49, 413

## NATURAL CARBON ABRASIVES 25

Abrasive or industrial diamonds.—Given new impetus by the war, the development of the harder metal alloys and the need for greater

<sup>&</sup>lt;sup>22</sup> Dasher, John, Fraas, Foster, and Gabriel, Alton, Mineral Dressing of Oregon Beach Sands, 1. Concentration of Chromite, Zircon, Garnet, and Ilmenite: Bureau of Mines Rept. of Investigations 3668, 1942,

<sup>19</sup> pp.

32 American Ceramic Society Bull., vol. 31, No. 11, November 15, 1942, p. 302; Manufacturers Record, vol. 112, No. 1, January 1943, p. 29.

32 Chemical and Metallurgical Engineering, vol. 49, No. 10, October 1942, p. 148.

33 See also chapter on Gem Stones of this volume.

The state of the s

accuracy and higher working speeds, have enlarged the scope of usefulness of diamonds. For many years diamonds have been essential in glass cutting and in rock drilling. Diamonds and diamond dust embedded in various matrices, such as powdered metal, plastics, and ceramic bonds, used in almost all manufacturing processes, are now much more important, quantitatively. In addition to their abrasive uses, diamonds are vitally needed because of their abrasionresistant qualities, which make them especially suitable for use as dies in drawing copper, tungsten, brass, and other wires or filaments and as atomizers in oil-burning equipment.

Although there have been reports in the trade press of the possible reopening of the long idle Arkansas diamond properties,26 by far the chief sources of abrasive or industrial diamonds now are Brazil and Belgian Congo. Other areas in Africa and South America also produce significant quantities of industrial diamonds. Imports of diamond dust into the United States in 1942 declined in value. Imports of bort increased over fourfold but were considerably under Diamonds for industrial use ("glaziers' and enthe 1937 figure. gravers', unset, and miners' diamonds") rose to 6,882,248 carats in 1941 and 11,203,704 carats in 1942 compared with 3,809,071 in 1940, a 194 percent increase within only 2 years. The average value per carat continued to decline, reflecting the greater use of smaller stones. The average values for 1942 and the 2 previous years were: 1942, \$1.98; 1941, \$2.17; and 1940, \$2.89.

The world production of diamonds in 1942 probably approximated that of 1941, when slightly less than 9,350,000 carats were produced. The 1941 figure was over one-third (34 percent) less than in 1940, when production reached 14,250,000 carats. In normal years about two-thirds of the annual world production of diamonds consists of industrial stones, although their value scarcely exceeds one-fifth of the total annual diamond output. Unlike gem diamonds, industrial diamonds are actually consumed. In normal times, over half the diamonds used in industry were destroyed after 12 months' continuous employment.27 Today the average life of industrial diamonds should be shorter, owing to the present intensity of work and the hardness of the alloys used for armament purposes.

The largest producing areas are in Africa-Belgian Congo, Gold Coast, Sierra Leone, and Angola together supplied 94 percent, by weight, of the total world output in 1941; South Africa and South-West Africa only 2 percent; and South America (Brazil, Venezuela, and British Guiana) 4 percent. 28 Of the 94 percent produced in Equatorial Africa, the output of the Gold Coast, Sierra Leone, and Angola represented 11, 9, and 8 percent of the world production.<sup>29</sup> Most of the Belgian Congo output came from the famous Beceka Sinclair 30 described mining and market conditions leading to the shut-down of the large South African diamond mines and the possible effect of the heavy demand for stones of industrial grade.

<sup>\*\*</sup> Engineering and Mining Journal, vol. 143, No. 11, November 1942, p. 96.

\*\* Economist, Industrial Diamonds: Vol. 143, No. 5160, July 18, 1942, pp. 88-89.

\*\* Ball, Sydney H., Diamond Production, In Symposium on Diamonds: Am. Mineral., vol. 23, No. 3, March 1943, pp. 141-150. (See esp. pp. 141-143.)

\*\* National Jeweler, August 1942, pp. 92, 163.

\*\* Sinclair, W. E., Diamond Mining in South Africa: Mining Mag. (London), vol. 66. No. 6, June 1942, pp. 251-256.

A new source of alluvial diamonds in the Ural Mountain region, U. S. S. R., was noted.<sup>31</sup>

Total sales of diamonds in 1942, according to market estimates, reached nearly £10,000,000 compared with £7,000,000 in 1941 and nearly £4,050,000 in 1938.32 A considerable shift in the relative positions of gem and industrial diamonds has occurred in the last year or two. Gem sales have been smaller but prices much higher than heretofore. The prices of industrial diamonds, however, by agreement, have remained unchanged since the start of the war. Indications therefore point to an appreciable advance in the sale of industrial stones.33 Factors in this increased importance of working diamonds, as above noted, are the volume and speed of war production, the greater hardness of armament alloys, with its attendant increase in replacement requirements, and the rapidly expanding

range of its usefulness.34

A group of papers covering changes and progress in the diamond industry during 1942 was published in the early part of 1943.35 World output, which is concentrated largely in the United Nations countries, and stocks were discussed by Ball.<sup>36</sup> After the Low Countries were invaded, the diamond-cutting industry was widely dispersed. Cutting industries have been established in Transvaal, Palestine, Brazil, Cuba, Puerto Rico, Great Britain, and the United States. gem-cutting establishments also have been producing specially shaped diamonds for tools or other industrial use. 37 Photomicrographic studies and the use of specially designed machines have resulted in marked improvements in the technique and speed of making drilling Although the present facilities for die drilling in the United States only about equal minimum requirements, expansion to provide for increased demand is under way.38 Wheel-dressing tools use more of the larger diamonds, but diamond core drilling consumes the larger portion of the smaller sizes, although the use of smaller stones in a cast or sintered head for dressing tools is increasing.39 The grinding of hard and brittle metals, nonmetals, and synthetics with bonded diamond products has increased enormously in 1942 compared with 1941. Research has resulted in improvements in the composition of metal bonds and in manufacturing processes and in the introduction of a new bond of the ceramic vitrified type with a high glass content.40

Excellent summaries of the many industrial applications of diamonds and diamond tools appeared in the Mining Journal 41 and in

<sup>31</sup> Averkin, A. A., and Shafranovskil, I. I., Diamonds from the New Diamond-Bearing Region of the Middle Ural Region: Mem. soc. russe minéral., vol. 68, 1939, pp. 357-369; Chem. Zentralb 1940, part II, pp. 2286-2287; Chem. Abs., vol. 36, No. 21, November 10, 1942, p. 6454.

32 Economist, Diamond Supplies: Vol. 144, No. 5193, March 6, 1943, pp. 309-310.

33 South African Mining and Engineering Journal, Diamonds in Industry—Increasing Demand for Stones: Vol. 53, pt. 1, No. 2586, August 22, 1942, p. 633.

34 Economist, Control of Industrial Diamonds: Vol. 142, No. 5145, April 4, 1942, pp. 478-479.

35 Kraus, Edward H., and others, Symposium on Diamonds: Am. Mineral., vol. 28, No. 3, March 1943, pp. 141-150.

36 Ball, Sydney H., Diamond Production: See Kraus, Edward H., and others, work cited in footnote 35, pp. 141-143.

37 Kaplan, Lazare, Gem Diamonds and Their Present Trends: See Kraus, Edward H., and others, work cited in footnote 35, pp. 143-145.

cited in footnote 35, pp. 143-145.

Shayne, Alexander, Diamond Dies: See Kraus, Edward H., and others, work cited in footnote 35,

pp. 145-148.

38 Slawson, Chester B., Diamond-Set Tools: See Kraus, Edward H., and others, work cited in footnote

<sup>&</sup>lt;sup>35</sup> 518WS0II, Chester B., Diamond-Ger 1003. 500 Index, Julian, 1988-149.

<sup>46</sup> Klein, A. A., Recent Development of Bonded Diamond Wheels: See Kraus, Edward H., and others, work cited in footnote 35, pp. 149-150.

<sup>41</sup> Mining Journal, Essential Role of Industrial Diamonds in Peace and War: Vol. 220, No. 5604, January 16, 1943, pp. 35-36.

一日の大学教教を記すると、大学のことのないで、中ではないよ

Foreign Commerce Weekly. 42 The latter also presented a brief description of localities, production, history, and uses of South American diamonds, especially the Brazilian product. The usefulness of the diamond in the mechanical engineering field was discussed.43 The experience of a large manufacturing plant in standardizing its diamond tools was published. 44 Information as to shapes and sizes of diamonds suited for truing and dressing purposes and methods of mounting diamonds individually and in diamond-impregnated tools were presented by Larson. 45 In order to cope with the expanding requirements for wheel-dressing tools, a more efficient method of setting the cutting edge was developed, making use of a vacuum for "positioning" the diamond.46

Padowicz 47 discussed the factors affecting die requirements and die performance in drawing copper wire at a large wire-drawing mill. Diamond failure was due not so much to wear as to breakage and chipping, caused by various strains having a possible correlation, in certain cases, to the angle of the drilling axis. Preparation, drilling, polishing, and mounting of diamond dies for use in wire drawing were described by Dudding, Eden, and Leeds. Patent history with respect to the invention of the rock drill and notes regarding the early use of diamonds for drilling purposes were presented by Grod-

zinski.49

## ARTIFICIAL ABRASIVES

Stimulated by the enormous activity in the munitions, shipbuilding, airplane, and other industries making war materials, the output of manufactured (artificial) abrasives in 1942 surpassed the former peak year (1941) by 33 percent in tonnage and 45 percent in value. Records also were established individually by all three classes of abrasives included in the Bureau of Mines figures. As in 1941, plants making crude aluminum oxide and silicon carbide in the United States and Canada operated at full capacity in 1942 and produced 61,681 short tons of silicon carbide valued at \$4,904,309 and 183,633 tons of aluminum oxide valued at \$12,719,337—an increase of 37 percent in tonnage of silicon carbide and 24 percent in tonnage of aluminum oxide. Operating at 72 percent of capacity, manufacturers of metallic abrasives (steel shot and grit) increased their sales in 1942 to 125,264 tons valued at \$6,232,842, a gain of 45 percent in quantity and 54 percent in value.

<sup>4</sup>º Foreign Commerce Weekly, Diamonds for Victory—South American Diamond Bullets Aid Democracy: Vol. 6, No. 3, January 17, 1942, pp. 3-5, 35.

4º South African Mining and Engineering Journal, Diamonds in Industry—Some Applications in the Engineering Field: Vol. 52, pt. II, No. 257, January 31, 1942, pp. 619, 621.

4º Machinery, Bulck Plant Standardizes Diamond Tools: Vol. 49, No. 8, April 1943, pp. 200-201.

4º Larson, E. T., Diamonds and Devices for Truing and Dressing: Grits and Grinds, vol. 33, No. 3, March 1942, pp. 1-7; pub. by Norton Co., Worcester, Mass.

4º Jameson, R. T., Setting Diamonds in Wheel-Dressing Tools: Am. Mach., vol. 86, No. 17, August 20, 1942, p. 884

<sup>45</sup> Jameson, R. T., Setting Diamonds in Wheel-Dressing 1005. Am. Macan, vol. 60, Atol. 1, August 1942, p. 884.
47 Padowicz, H. N., Diamond Dies for the High-Speed Drawing of Copper Wire: Bell Sys. Tech. Jour., vol. 21, No. 1, June 1942, pp. 20-36.
48 Dudding, B. P., Eden, C. G., and Leeds, R. E., Diamond Dies for Wire Drawing: Metal Ind., vol. 61, No. 21, November 6, 1942, pp. 290-293; condensed in Metals and Alloys, vol. 17, No. 2, February 1943, pp. 358.
49 Grodzinski, P., Invention of the Rock Drill: Canadian Min. Jour., vol. 16, No. 1, January 1942, pp. 15-16.

Crude artificial abrasives sold, shipped, or used, from manufacturing plants in the United States and Canada, 1938-42 1

FIN	Silicon carbide 2		Alumin	Aluminum oxide 2		Metallic abrasives		Total	
Year	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	
1938 1939 1940	25, 346 24, 206 33, 042 44, 962	\$1, 904, 925 1, 713, 207 2, 359, 876 3, 325, 928	53, 220 50, 468 98, 531 147, 759	\$3,098,132 3,047,337 5,464,986 9,067,732	25, 771 42, 015 50, 016 86, 309	\$1, 234, 977 1, 743, 859 2, 317, 829 4, 050, 659	104, 337 116, 689 181, 589 279, 030	\$6, 238, 034 6, 504, 403 10, 142, 691 16, 444, 319	

I Bureau of Mines not at liberty to publish data for United States separately.
Production; includes material used for refractories and other nonabrasive uses.

Production of silicon carbide and aluminum oxide is concentrated largely in the Niagara Falls region of Canada and the United States; some output of aluminum oxide comes from Quebec, Canada, and Alabama. "White High Purity or Special" aluminum oxide produced in 1942 totaled 31,665 short tons valued at \$4,509,486, compared with 22,659 tons valued at \$2,676,753 in 1941, an increase of 40 percent in tonnage and 52 percent in dollars. Estimated percentage of total consumption of silicon carbide for nonabrasive or refractory purposes in 1942 rose to 35 percent, compared with 32 percent in 1941 and 1940 and 29 percent in 1939. Similar percentages for aluminum oxide were 3 percent in 1942 and 1941, 2 percent in 1940, and 4 percent in

Metallic abrasives, including steel grit and shot but excluding steel wool, are manufactured in Michigan, New Hampshire, Ohio, and Pennsylvania. An illustrated article describing the plant and manufacturing process of the Harrison Abrasive Corporation, Manchester, N. H., appeared in 1942.50 A flowing stream of molten steel is broken up by jets of steam. The resulting globules and irrregular particles fall into water, which chills and hardens them. The shot are graded into 16 commercial sizes, and the irregular pieces are crushed and screened into 12 sizes and marked as grit. The material is sold largely for cleaning castings and working stone.

The properties and uses of silicon carbide, aluminum oxide, and boron carbide and particularly their application and employment in the various types of grinding wheels were described in a report printed during 1942.<sup>51</sup> Manufactured abrasives and their utilization in grinding wheels also were discussed by Arend.<sup>52</sup> A description was given of the preparation of crude abrasive aluminum oxide ore received at the manufacturing plant of the Abrasive Co., Philadelphia, Pa., from its electric furnaces in Canada, beginning with the crushing and pulverizing operations through magnetic separation and elaborate grading to the manufacture of the principal end product (abrasive

<sup>50</sup> Park, Allen, S., Chilled Steel Shot and Grit: Compressed Air Mag., vol. 47, No. 3, March 1942, pp.

Far, Anen, S., Odmed Steel Show and offic. Compressed Air Mag., vol. 47, No. 3, March 1942, pp. 6884-6888.
 Cooper, Hermon C., Modern Abrasives: Jour. Chem. Education, vol. 19, No. 3, March 1942, pp. 122-127.
 Arend, A. G., Grinding Wheels; Composition of Abrasives from Electric Furnaces: Electrical Rev. (London), vol. 131, September 25, 1942, pp. 391-392.

wheels) by controlled firing schedules.<sup>53</sup> About 75 percent of the firm's business is in aluminous oxide products and the remainder in abrasives made of silicon carbide, which is received at the Philadelphia mill in the form of grain.

# MISCELLANEOUS MINERAL ABRASIVE MATERIALS

In addition to the natural and manufactured abrasive materials discussed, many other mineral substances have abrasive uses. Various oxides, including tin oxide, rouge, crocus, chromium oxide, magnesium oxide, and manganese oxide, are utilized as polishing agents. Finely ground as well as calcined clays, high-grade lime, talc, river silt, slate flour, whiting, feldspar, and other substances also are used as abrasives.

## FOREIGN TRADE 54

Imports of corundum ore in 1941 reached 5,865 short tons, slightly over double the 1940 imports and the highest figure at least since 1924. (Before 1924 imports of corundum and emery ere were not shown separately in Mineral Resources volumes.) Imports in 1942, however, declined 19 percent to 4,739 tons. As in 1941, no emery ore was received, and receipts of pumice were at an extremely low level. Imports of "flint, flints, and flint stones, unground," in 1942 were about one-quarter of those received in 1941. Imports of bort increased sharply. Imports of smaller diamonds, comprizing "glaziers' and engravers', unset, and miners' diamonds," totaled 11,203,704 carats valued at \$22,154,076 in 1942, compared with 6,882,248 carats valued at \$14,908,809 in 1941. The imports in both years were greatly in excess of those in the industrially active years 1940 and 1939. The influence of the expanded war production, as well as the ever-widening utilization of diamonds in industry, contributed largely to this indicated increased consumption.

The value of exports of natural abrasive materials in 1942 totaled \$6,684,352, the highest year since 1920. The value of grindstones exported in 1942 rose 20 percent over 1941 to \$224,998. The chief increase in value of exports, however, was in emery or corundum abrasive wheels, which were higher in 1942 than in any year since 1918. The value of exports of all other natural abrasives and abrasive products in 1942, though more than double that of 1939 and 1940,

declined slightly from the 1941 value.

<sup>&</sup>lt;sup>13</sup> Ceramic Industry, Abrasive Industry Plays an Important Part in the War Program: Vol. 39, No. 4, October 1942, pp. 66, 68, 70, 72.

<sup>14</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Abrasive materials imported for consumption in the United States, 1940-42, by kinds

위에 있다. 하는 물로 있는 것으로 한 번째 되는. 기계 하는 사람들은 <mark>무료</mark> 를 하는 기를 받는 것	1	940	1	941	19	<b>)42</b>
Kind	Quantity	Value	Quantity	Value	Quantity	Value
Millstones and burrstones: Bound up	1 10 10					
into millstonesshort tons	40	\$2, 167	12	\$685	2	\$153
Grindstones, finished or unfinished						
short tons Hones, oilstones, and whetstones	634	18, 275	511	14, 745	491	17,719
short tons.	37	42, 482	22	41, 168	48	59, 196
Emery:		1		7.		00,20
Grains, ground, pulverized, or re-	5, 718	73, 935				
finedpounds_	(1)	(1)	(1)	(1)	(1)	(1)
Paper and cloth of emery or corun-	N 1					9
dum	(²)	91, 112	(2)	165, 544	(2)	156, 846
Wheels, files, and other manufac- tures of emery or corundum or	100	1				
garnetpounds_	4, 348	2,473	786	476	5, 757	1, 329
Corundum (see also "Emery"):	0.000	105 050		007 100		
Oreshort tons_ Grains, ground, pulverized, or re-	2, 922	165, 270	5, 865	287, 102	4, 739	260, 783
inedpounds	1 134, 606	19,262	1 102, 906	1 4, 021	1124, 362	17, 001
Tripoli and rottenstoneshort tons	227	3, 767	431	9, 116	231	4,826
Pumice: Crude or unmanufactured_do	3,758	20,771	43	987	67	1 201
Manufactures of, or of which pum-	0,100	20,771	10	301	07	1, 391
ice is the component material of	<b>.</b>			the state of		100
chief value Diamond:	(8)	6, 468				
Bortcarats_	785	19,660	502	16, 196	2, 147	26, 559
Dustdo	(3)	2, 515	(3)	2,805		776
Glaziers' and engravers', unset, and miners'	2 900 071	11, 026, 563	6 000 040	14 000 000	11 000 704	00 154 050
Flint, flints, and flint stones, un-	9, 000, 071	11, 020, 503	0, 002, 248	14, 908, 809	11, 203, 704	22, 154, 076
groundshort tons_	2,840	32, 397	1, 467	18, 494	376	5, 683
		11, 517, 117		15, 470, 148		22, 696, 338

Emery included with corundum; not separately classified.
 1,562 reams in 1940, 2,975 reams in 1941, 1,787 reams in 1942; weight not recorded.
 Quantity not recorded.

Value of domestic abrasive materials exported from the United States, 1938-42

Material	1938	1939	1940	1941	1942
Grindstones Abrasive wheels, emery and corundum All other natural abrasives, whetstones.	\$122, 720 116, 456	\$173, 575 125, 303	\$215, 156 179, 514	\$187, 621 144, 393	\$224, 998 3, 665, 386
hones, etc	835, 894	1, 116, 711	1, 211, 291	2, 887, 628	2, 793, 968
	1, 075, 070	1, 415, 589	1, 605, 961	3, 219, 642	6, 684, 352

## SULFUR AND PYRITES

By G. W. Josephson and M. S. Jensen<sup>1</sup>

### SUMMARY OUTLINE

	Page	Sulfur—Continued.	Page
General summary	1349	Consumption and uses	1354
Salient statistics	1351	Foreign trade	1355
Sulfur	1351	World production	1357
Domestic production	1351	Pyrites	1359
Review by States	1351	Domestic production	1359
Recovery as byproduct	1352	Review by States	1359
Stocks	1353	Foreign trade	1360
Price	1353	World production	1361

## GENERAL SUMMARY

For the sulfur industry, 1942 was a year of activity and readjustment to meet wartime demands. Except for Great Britain, which still depends largely on imports, the major belligerents enjoyed adequate supplies of sulfur and its primary compounds derived either from natural deposits or recovered as industrial byproducts. Many countries, especially those in isolated or exposed positions like New Zealand, Turkey, and Sweden, began to feel a shortage as their stock piles became depleted and imports were reduced by blockade or deficiency of shipping facilities.

Almost everywhere realization of the crucial role being played by sulfur in industry led to the adoption of policies aimed at achieving national self-sufficiency. Production from local deposits or from previously untapped byproduct sources was encouraged by high

prices or subsidies.

As most of the output of the United States sulfur industry is marketed in North America, the decline in export activity was not a serious factor. On the other hand, Italian and Spanish producers, being largely dependent on foreign markets, found that they had lost free access to many of their usual customers, and fully compensating demand did not develop in Europe. Activity was stimulated among the smaller producers, like Chile, Bolivia, Australia, and Canada, which are conveniently located to supply the neglected markets.

In the United States, as in many other countries, new production and consumption records were attained. Mine shipments were not as high as in 1941, owing principally to completion of stock-piling programs. Although sulfur production capacity was ample and stock piles adequate for at least 1½ years' consumption requirements were above ground, conditions in the industry were observed closely by various Government agencies. Transportation was an outstanding

The state of the s

The second of th

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

problem. Price structures along the East coast were based upon low-cost coastwise water delivery of crude sulfur. With the advent of submarine attacks and requisitioning of ships for other service, sulfur was largely diverted to more expensive railroad and barge routes. Sufficient equipment was available in 1942 to carry sulfur and its




FIGURE 1.—Domestic production, shipments for domestic consumption, exports, and imports of crude sulfur, 1900-1942.

compounds, but some concern was expressed as the tonnage of acids increased. On December 5, 1942, the War Production Board placed sulfuric acid under allocation to permit prompt action in case of emergency and to assure supplies for explosives requirements. Sulfur consumers were urged to maintain large stocks as insurance against future transportation bottlenecks. Prices of sulfur and its compounds remained substantially stable during the year.




FIGURE 2.—Domestic production and imports of pyrites, 1900-1942.

On June 26, 1942, an indictment charging a violation of the antitrust laws in the manufacture, distribution, and sale of sulfuric acid was returned against 15 companies and 37 individuals. However, upon the representation of the Secretaries of War and Navy that trial of the case would interfere with the war program, the Attorney General requested its postponement until after the war. The defendants agreed to this.<sup>2</sup>

<sup>&</sup>lt;sup>2</sup> Source: Englehart, Otto T., Special Assistant to the Attorney General, U. S. Department of Justice.

The story of the American sulfur industry was told by William Haynes in a book published in 1942, entitled "The Stone That Burns."

Salient statistics of the sulfur industry in the United States, 1925-29 (average) and 1939-42

	1925-29 (average)	1939	1 <del>94</del> 0	1941	1942
		1.5		44.34	
Sulfur: Production of crude sulfurlong tons	1, 951, 034	2, 090, 979	2, 732, 088	3, 139, 253	3, 460, 686
Shipments of crude sulfur:					
For domestic consumptiondo For exportdo	1, 397, 411 707, 175	1, 605, 998 627, 819	1, 812, 274 746, 468	2, 671, 946 729, 464	2, 560, 060 568, 499
Total shipmentsdo	2, 104, 586	2, 233, 817	2, 558, 742	3, 401, 410	3, 128, 559
Oredo	1,896	35	(1)		
Otherdo	295	13, 941	27, 845	28, 631	25, 632
Exports of treated sulfurdo	11, 956	25,005	19, 745	31,312	17, 030
Producers' stocks at end of year_do Price of crude sulfur f. o. b. mines	2, 413, 000	4,000,000	4, 200, 000	3, 900, 000	4, 300, 000
per long ton	\$17.50	\$16	\$16	\$16	\$16
Pyrites:	(4.1.3.)				
Production long tons.	273, 936	519, 497	626, 640	2 645, 257	720, 363
Importsdo	372, 958	482, 336	407, 004	368, 838	300, 139
Price of imported pyrites c. i. f. Atlantic	10.10	10.10	10.10		12
ports cents per long-ton unit	12–13	12-13	12-13	12	12
Sulfuric acid: Production of byproduct sul-	12.67.60				191
furic acid (60° B.) at copper and zinc	1, 118, 453	778, 441	840, 937	915, 989	960, 764
histingphote cons	1, 110, 400	110, 441	010, 001	510, 505	550, 101

<sup>1</sup> Less than 1 ton. 2 Revised figures.

## SULFUR

### DOMESTIC PRODUCTION

Production of crude sulfur in the United States in 1942 attained a new record of 3,460,686 long tons, exceeding the previous high, established in 1941, by 10 percent. Mine shipments, adversely influenced by export restrictions and completion or modification of domestic stock-piling programs, were 8 percent lower than in 1941. Approximately 1,600 long tons of sulfur-bearing ore, containing 10 to 50 percent sulfur, mined in Colorado and Texas for agricultural purposes, are not included in the sulfur total.

## REVIEW BY STATES

More than 83 percent of the native sulfur mined in the United States in 1942 came from deposits in Texas and over 16 percent from Louisiana. The remaining fraction of 1 percent was supplied by mines in California and Utah.

Sulfur produced and shipped in the United States, 1938-42

	· 140	Produced (	Shipped				
Year	Texas	Louisiana	Other States 1	Total	Long tons	Approxi- mate value	
1938	2, 060, 845 1, 665, 400 2, 212, 839 2, 596, 731 2, 885, 621	328, 405 422, 600 512, 935 533, 620 570, 345	4, 158 2, 979 6, 314 8, 902 4, 720	2, 393, 408 2, 090, 979 2, 732, 088 3, 139, 253 3, 460, 686	1, 628, 847 2, 233, 817 2, 558, 742 3, 401, 410 3, 128, 559	\$27, 300, 000 35, 500, 000 40, 900, 000 54, 400, 000 50, 100, 000	

<sup>1 1938-40</sup> and 1942: California and Utah; 1941: California.

California.—Pacific Sulphur Co. produced sulfur from the Crater claims at Bigpine, Inyo County.

Louisiana.—Freeport Sulphur Co. supplied the entire Louisiana output from Grande Ecaille, Plaquemines Parish. Production from

this dome continued to increase steadily.

Texas.—As indicated in the following table (compiled from information issued by the Texas State Comptroller's Office), four organizations produced practically all the Texas output. Duval Texas Sulphur Co. reported production from Orchard Dome, Fort Bend County; Freeport Sulphur Co. from Hoskins Mound and Jefferson Lake Sulphur Co., Inc., from Clemens Dome, both in Brazoria County; and Texas Gulf Sulphur Co., from Boling Dome, Wharton County. The Pecos Orla Sulphur Co. mined sulfur ore at the Michigan claims in Culberson County.

Sulfur produced in Texas in 1942, by companies, in long tons

Company	First quarter	Second quarter	Third quarter	Fourth quarter	Total
Texas Gulf Sulphur Co Freeport Sulphur Co Jefferson Lake Sulphur Co., Inc Duval Texas Sulphur Co	545, 313- 118, 350 13, 096 48, 820	592, 191 115, 280 8, 575 58, 660	564, 850 113, 815 21, 695 39, 305	471, 028 97, 055 33, 218 44, 088	2, 173, 382 444, 500 76, 584 190, 873
가능하는 것 같아 하지만, 그 사이스 중에 되는 것 같아 있습니다. 일본이 사실한 말이 되는 것 같아 보는 사람들이 되었다.	725, 579	774, 706	739, 665	645, 389	1 2, 885, 339

<sup>&</sup>lt;sup>1</sup> Total differs slightly from Texas production figure in preceding table because certain reports to Texas Comptroller are closed for year on December 25, whereas Bureau of Mines total covers calendar year.

Utah.—Pacific Sulphur Co. produced sulfur in Beaver County.

### RECOVERY AS BYPRODUCT

The treatment of copper and zinc ores yields large quantities of sulfur, which are recovered at the mills as pyrites concentrates or at the smelters as sulfuric acid or elemental sulfur. The production of pyrites concentrate is discussed in the Pyrites section of this chapter. In smelting copper and zinc concentrates, sulfur is driven off as a constituent of gases, principally sulfur dioxide, which are used in the manufacture of sulfuric acid at many smelters. The equivalent of about 190,000 long tons of sulfur was recovered as sulfuric acid annually from this source during the 5 years ended in 1942. Such sulfur is not included in the sulfur-production figures for the United States, but the following table shows the output of byproduct acid at both copper- and zinc-smelting plants.

Byproduct sulfuric acid <sup>1</sup> (expressed as 60° B.) produced at copper and zinc plants in the United States, 1938-42, in short tons

	1938	1939	1940	1941	1942
Copper plants 1 Zinc plants	220, 297 466, 879	249, 569 528, 872	254, 025 586, 912	243, 812 672, 177	265, 522 695, 242
	687, 176	778, <b>4</b> 41	840, 937	915, 989	960, 764

¹ Includes small quantity of sulfuric acid produced as byproduct in roasting of high-sulfide gold and silver concentrates.

The recovery of sulfur or sulfur compounds from coke-oven, refinerystill, natural, and other fuel gases is receiving increasing attention. In many foreign countries these processes are encouraged as a step toward self-sufficiency and in the United States as a means of profitably utilizing a waste product or of conserving natural resources. Exemplifying this activity, a description was published in 1942 of progress in attempts to extract elemental sulfur from the enormous reserves of sour natural gas available in southwest Arkansas; here, removal of the sulfur has the additional advantage of greatly improv-

ing the quality and value of the fuel gas itself.3

Most of the elemental sulfur recovered from gas purification comes from operations using the Thylox process; relatively small quantities are recovered with the Ferrox and Nickel processes. Production in 1942 (reduced to 100 percent sulfur) totaled 5,125 long tons; 4,520 tons valued at \$168,333 were shipped. Output came from Illinois, Maryland, Massachusetts, Missouri, New Jersey, New York, Wash-William (1988). ington, West Virginia, and Wisconsin; Massachusetts and New York were the largest producers. The product was marketed as a paste containing 37 to 50 percent sulfur or as dried relatively pure sulfur. The fine particle size of this material makes it valuable as a fungicide and insecticide, and these uses absorb most of it. Of the 1942 shipments (reduced to 100 percent sulfur), 37 percent was in the form of paste, and the remainder was dried sulfur.

Sulfur is also removed from fuel gases in the form of hydrogen sulfide, most of which is either converted into sulfuric acid or burned as fuel. The hydrogen sulfide recovered in 1942 came from plants using the phenolate, phosphate, and Girbotol processes. In 1942 the

recovery of hydrogen sulfide (largely for sulfuric acid manufacture) was equivalent to 19,097 long tons of sulfur; the plants were in California, New Jersey, and Pennsylvania.

The figures covering the byproduct yield of sulfur from gas purification are not included in the sulfur production figures for the United States.

## STOCKS

Stocks of crude sulfur held at the mines increased during the year and on December 31 amounted to 4,300,000 long tons. In addition, the producing companies hold substantial tonnages at other locations or in transit. The combined total of all producer-owned stocks at the end of the year was about 5,114,000 long tons, 9 percent more than on December 31, 1941. Although exactly comparable figures are not available for past years, it is apparent that producers' stocks are at or near an all-time high.

#### PRICE

Crude sulfur was quoted by trade journals at \$16.00 per long ton f. o. b. mines throughout 1942. On May 11 (announced April 28) the Office of Price Administration froze prices at the maximum levels of March 1942. Subsequently there were intermittent reports of efforts to both raise and lower prices, but no change was authorized. Refined-sulfur prices, reflecting increased freight costs, were raised approximately 10 percent by some manufacturers before the General Maximum Price Regulation was established, but little or no change took place thereafter.

Sulfuric acid, 66° B., was quoted by journals at \$16.50 per short ton at works in tank cars. The General Maximum Price Regulation

Lee, James A., Sulphur from Arkansas Sour Gas: Chem. and Met. Eng., vol. 49, No. 6, June 1942, p. 80.

established ceiling prices, which were not disturbed. However, some acid producers were able to increase their over-all realization somewhat by bringing some of their lower-priced sales closer to the standard ceiling.

## CONSUMPTION AND USES

The apparent domestic consumption of sulfur in 1942 increased 6 percent over 1941, attaining a new record. This figure may be slightly low, as it does not allow for stock piles accumulated by consumers during 1941.

The following table shows the apparent domestic consumption of sulfur during the past 5 years.

Apparent consumption of sulfur in the United States, 1938-42, in long tons

	1938	1939	1940	1941	1942
Shipments <sup>1</sup>	1, 628, 847 2, 603	2, 233, 817 13, 976	2, 558, 742 27, 845	3, 076, 038 28, 631	3, 032, 043 26, 018
[일종 휴 현기 등급하다 그는 생각	1, 631, 450	2, 247, 793	2, 586, 587	3, 104, 669	3, 058, 061
Exports: Crude	579, 107 12, 707	627, 819 25, 005	746, 468 19, 745	729, 464 31, 312	568, 499 17, 030
5 (14 1 - 14 1 - 14 1 1 1 1 1 1 1 1 1 1 1 1	591, 814	652, 824	766, 213	760, 776	585, 529
Apparent consumption	1, 039, 636	1, 594, 969	1, 820, 374	2, 343, 893	2, 472, 532

<sup>1 1938-40:</sup> Mine shipments; 1941-42: Apparent shipments to consumers.

The pattern of industrial sulfur consumption has been estimated by Chemical and Metallurgical Engineering as follows:

Sulfur consumed in the United States, 1938-42, by uses, in long tons 1

Use	1938 1	1939	1940	1941	1942
Chemicals Fertilizer and insecticides. Pulp and paper Explosives Dyes and coal-tar products Rubber Paint and varnish Food products Miscellaneous	484,000 220,000 174,000 50,000 40,000 29,000 50,000 5,500 47,500	695, 000 370, 000 240, 000 64, 000 46, 000 43, 000 49, 000 6, 000 82, 000	800,000 410,000 320,000 74,000 51,000 47,000 54,000 6,000 86,000	2 1, 060, 000 450, 000 360, 000 2 83, 000 65, 000 65, 000 6, 000 95, 000	\$1,570,000 500,000 365,000 \$90,000 60,000 35,000 70,000 6,000
	1, 100, 000	1, 595, 000	1,848,000	2, 239, 000	2, 816, 000

<sup>&</sup>lt;sup>1</sup> Figures for 1938 not truly representative of consumption but rather of shipments to these specified indusies. Consumers carried over large stocks from 1937, therefore consumption in 1938 was larger than total

Under recent peacetime conditions approximately 70 percent 5 of the brimstone consumed in the United States was converted into sulfuric acid, and the wartime demands of the explosives and petroleum industries have probably increased the proportion. Production of sulfuric acid, calculated as 50° B., is estimated to have increased to 12,520,000 short tons in 1942, 14 percent above the 1941 output of 10,944,000 tons.6

<sup>&</sup>lt;sup>1</sup>To avoid disclosing estimated consumption of sulfur in direct defense applications, such as military explosives, sulfur so used in 1941 and 1942 is included under "Chemicals."

From information supplied by Office of Price Administration.
Texas Gulf Sulphur Co., Sulphur, An Essential to Industry and Agriculture: 1940, 45 pp.
Chemical and Metallurgical Engineering, Sulphuric Acid and Sulphur: Vol. 50, No. 2, February 1943,

Chemical and Metallurgical Engineering has estimated the consumption of sulfuric acid, by industries, from 1938 through 1942 as follows:

Sulfuric acid (expressed as 50° B.) consumed in the United States, 1938-42, by industries, in short tons

Industry	1938	1939	1940	1941	1942
Fertilizer Petroleum refining Chemicals Coal products Iron and steel Other metallurgical Paints and pigments Explosives Rayon and cellulose film Textiles Miscellaneous	1, 900, 000 1, 100, 000 800, 000 585, 000 590, 000 430, 000 140, 000 355, 000 355, 000	1, 970, 000 1, 210, 000 975, 000 740, 000 980, 000 570, 000 520, 000 160, 000 116, 000 384, 000	2, 260, 000 1, 260, 000 1, 120, 000 1, 120, 000 1, 300, 600 640, 000 580, 000 170, 000 470, 000 125, 000 360, 000	2, 500, 000 1, 400, 000 1 1, 790, 000 940, 000 1, 500, 000 700, 000 1 190, 000 505, 000 500, 000	2, 950, 000 1, 650, 000 1 2, 250, 000 970, 000 1, 600, 000 1 195, 000 625, 000 145, 000 530, 000

<sup>&</sup>lt;sup>1</sup> To avoid disclosing estimated consumption of acid in direct defense applications, such as military explosives, acid so used in 1941 and 1942 is included under "Chemicals."

It is estimated that industry as a whole used 13 percent more sulfuric acid in 1942 than in 1941. The largest increases in consumption were made in the petroleum, fertilizer, and chemical (which includes military explosives) industries—18, 18, and 26 percent, respectively. With the exception of textiles, which decreased 12 percent, other

industries enjoyed modest increases of 3 to 12 percent.

Two of the more significant applications of sulfuric acid during this wartime period are in the production of aviation gasoline by the alkylation process and in military explosives. Large expansion programs in these fields are making themselves felt both as volume consumers of strong acids and as producers of spent acids. Each locality has its individual spent-acid problems, which must be solved by regeneration, consumption in some intraplant operation in which weaker acids are satisfactory, or sale to other less critical industries. Whatever the solution, readjustments in the normal handling and distribution of acids are required. Local consumption or regeneration of spent acid was advocated as a means of alleviating the steadily growing demands on railroad facilities. Rail shipments of sulfuric acid have more than doubled during the past 2 years.

The versatility of sulfur in war is illustrated by the practice of stimulating the flow of gum from southern turpentine pines by painting

the tap wounds with sulfuric acid.

That sulfur continued to occupy a prominent position in research laboratories is indicated by its use in synthetic rubber, and in less publicized discoveries, such as the compound tetraethyl thiuram monosulfide (a preventive of a serious poultry disease).

### FOREIGN TRADE

As a result of the stringent shipping situation, exports of crude and treated sulfur were, respectively, 22 and 46 percent lower than in 1941. The accompanying table of exports by countries reveals the changes in pattern of distribution caused by the war.

<sup>&</sup>lt;sup>7</sup> Science News Letter, vol. 42, No. 5, August 1, 1942, p. 72.

Imports of elemental sulfur (principally from Canada) decreased 10 percent. Imports of sulfuric acid (also largely from Canada) totaled 13,689 short tons and exports 9,679 short tons.

Sulfur exported from the United States, 1941-42, by countries

		Cr	ude		Crushed, ground, refined, sublimed, and flowers of				
Country	1941		1.,	1942	1941		1942		
	Long tons	Value	Long tons	Value	Pounds	Value	Pounds	Value	
North America: Canada Central America Mexico Newfoundland West Indies	208, 915 210 5, 900 11, 489 17, 295	\$3, 880, 002 6, 182 113, 274 195, 573 294, 052	4,489 14,822	\$6, 251, 551 3, 294 87, 863 311, 930 212, 721	8, 302, 636 650, 309 3, 259, 937 2, 910 656, 784	\$189, 291 15, 957 62, 950 116 20, 436	8, 151, 119 589, 188 3, 907, 260 4, 500 370, 377	\$224, 702 14, 403 73, 970 207 16, 878	
	243, 809	4, 489, 083	329, 597	6, 867, 359	12, 872, 576	288, 750	13, 022, 444	330, 160	
South America: Argentina Brazil Chile Colombia Equador	10, 944		16, 338 16, 582 230	294, 975 333, 984 4, 913	119, 205 4, 781, 876 12, 800 573, 656 31, 297	20, 649 104, 339 387 14, 139 1, 143	716, 494 39, 580	15, 709 92, 668 24 19, 614 1, 261	
Peru Uruguay Venezuela Other South America	3, 170 299	54, 340 6, 950	1, 224 20	39, 368 501	137, 193 139, 900 148, 237 7, 552	2, 999 4, 136 5, 330 214	109, 298 16, 393	3, 177 13, 878 2, 938 482	
	14, 413	273, 958	34, 394	673, 741	5, 951, 716	153, 336	6, 032, 700	149, 748	
Europe: Greece Sweden United Kingdom 1 Other Europe	296, 498 21	4, 622, 371 801	121, 807	1, 888, 005	19, 651, 804 26, 100 4, 859, 614 9, 918	274, 551 640 104, 996 595		76, 624 2, 372	
	296, 519			1, 888, 005		380, 782	3, 230, 794	78, 996	
Asia: Arabia British Malaya Burma China Hong Kong India and Dependencies <sup>2</sup> Indochina, French	1, 080 641 234 28, 774	32, 800 14, 598 7, 162 565, 135			2, 973, 210 701, 330 154, 280 1, 125, 200 1, 012, 324 10, 051, 463 334, 450	30, 401 23, 093 2, 752 18, 896 21, 139 189, 970 9, 377	66, 352 112 2, 500 8, 246, 626	998 38 1, 018	
Iran Netherlands Indies Other Asia	2,500 1,800 1,271	32,400		l	362, 096 657, 164	13, 035 16, 522	3, 997, 000 178, 350 403, 431	36, 456 3, 978 10, 679	
	36, 300	749, 059	17, 609	406, 699	17, 371, 517	325, 185	12, 894, 371	276, 432	
Africa: Belgian Congo British East Africa Egypt Madagascar Mozambique Nigeria Union of South Africa Other Africa	20, 947	380, 565		3, 555 77	144, 319 1, 503, 323 2, 212, 534 440, 050 99, 746 16, 056 3, 621, 021 239, 884	2, 978 31, 998 52, 261 8, 658 5, 432 474 83, 331 4, 475	700, 752 355, 582 	12, 093 17, 509 7, 530 1, 057 28, 689 198	
	21, 381	395, 137	19, 595	351,002	8, 276, 933	189, 607	2, 687, 404	67, 073	
Oceania: Australia New Zealand Other Oceania	53, 232 63, 810	925, 050 1, 064, 609				18, 435 4, 303 285	229, 739	1, 703 7, 416 70	
	117, 042	1, 989, 659	45, 497	761, 684	1, 119, 042	23, 023	280, 338	9, 189	
	700 101	10 700 000	F.CO. 400	10 040 400	70, 139, 220	1 000 000	20 140 051	911, 59	

<sup>&</sup>lt;sup>1</sup> United Kingdom of Great Britain and Northern Ireland.
<sup>2</sup> British India.

Sulfur imported into and exported from the United States, 1938-42

		Imp	oorts		Exports				
Year	Ore		In any form, n. e. s.		C	rude	Crushed, ground, refined, sublimed, and flowers of		
	Long tons	Value	Long tons	Value	Long tons	Value	Long tons	Value	
1938 1939 1940 1941 1941	51 35 (1)	\$562 445 5	2, 552 13, 941 27, 845 28, 631 25, 632	\$71, 903 250, 422 473, 052 487, 758 442, 811	579, 107 627, 819 746, 468 729, 464 568, 499	\$10, 378, 991 10, 771, 751 13, 041, 911 12, 520, 068 10, 948, 490	12, 707 25, 005 19, 745 31, 312 17, 030	\$469, 773 909, 974 780, 968 1, 360, 683 911, 598	

<sup>1</sup> Less than 1 ton

### WORLD PRODUCTION

Censorship restrictions of the belligerent nations have for several years eliminated publication of their production statistics, making any estimate very arbitrary. Available figures are shown in the following table. Judging from the meager information at hand, world production of elemental sulfur probably exceeded 4,300,000 long tons in 1942.

World production of native sulfur, 1937-42, by countries, in long tons 1 [Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
Bolivia (exports)	1,712	1,632	2, 126	4, 065	2, 315	3, 535
Ecuador	16, 766 54	20, 959 68	26, 999 72	28, 997 (3)	24, 784 (3)	42, 900
France (content of ore)	157	140	(3) 12		3	(3)
Greece	67	75	(3)	(3) (3)	8	(3)
Guatemala	ĭi l	15	12	11	(8)	3
Italy (crude)4	338, 101	374, 339	(3)	(3)	(3)	(8)
Japan	138, 283	(3)	(3)	(3)	(8)	(3)
Mexico	(3)	49	(3)	(8)	(8)	(3)
Netherlands East Indies	12, 474	15, 986	17, 293	16, 908	(3)	(3)
Palestine	494	1, 196	829	1, 248	(3)	(3)
Peru	1,551	1,944	569	610	923	(3)
Spain 5 Turkey	1,950	2,050	(3)	(3)	(3)	(3)
United States	2, 229 2, 741, 970	3, 684 2, 393, 408	2,560	0 700 000	0 100 000	0 460 600
Omied States	4, 741, 970	2, 393, 408	2, 090, 979	2, 732, 088	3, 139, 253	3, 460, 686
Estimated world total.	3, 400, 000	3, 100, 000	2, 900, 000	3, 500, 000	4,000,000	4, 300, 000

<sup>\*</sup>Native sulfur believed to be produced also in Argentina, China, Cuba, India, Iran, Taiwan, and U.S. S. R., but quantity unknown.

2 In addition, 1,050 tons of sulfur rock (40-80 percent sulfur) reported for 1937.

3 Data not available.

Bolivia.—Active demand and high prices are stimulating expansion of both Concepción and San Pablo de Napa, the latter being the principal Bolivian producer.8

Canada.—Substantial quantities of byproduct elemental sulfur were produced for domestic consumption and export; 25,071 long tons were exported to the United States.

Chile. - Surface deposits of sulfur occur along the Andes from the Peruvian frontier to about 36° south latitude. The principal mines

<sup>&</sup>lt;sup>4</sup> In addition, following quantities of sulfur rock reported—1937: 19,793 tons; 1938: 16,545 tons. Similar data not available for later years. Estimated sulfur content of ore, excluding sulfur made from pyrites.

Engineering and Mining Journal, vol. 143, No. 7, July 1942, p. 100.

are around Mount Tacora in Arica and in Antofagasta Province near the Bolivian border.9 Wartime shipping restrictions put Chile's sulfur industry in a good competitive position in the Argentine, Uruguayan, and Brazilian markets, even at high prices. Old operations were active, and the Corporación de Fomento granted capital to open a new deposit in Arica. 10 Although the present situation is satisfactory, the industry is still not particularly profitable, and it is realized that the postwar outlook depends on the development of a more efficient method of treating these ores. The problem is complicated by the fact that these operations, in barren terrain 13,000 to 19,000 feet above sea level, depend on a local resinous moss for fuel.11 Destructive harvesting is seriously threatening the supply. As coal would have to be brought, at considerable expense, by steamer, rail, and pack horse from south central Chile, the situation is causing some Chilean authorities are sponsoring less destructive methods of harvesting and a program to determine whether or not the plant can be domesticated and cultivated.

Germany.-Although Sicily's sulfur supplies were available to Germany in 1942, the somewhat meager information obtainable indicates it was not necessary to draw heavily on the Italian deposits. Germany's sulfur needs were apparently satisfied by its well-developed byproduct installations and plants using pyrites or calcium sulfate as a The literature indicates that German technology raw material. reported progress in developing efficient sulfur burners and processes that recover sulfur from very low concentrations in coke-oven and

coal-distillation gases.12

Great Britain.—A committee of the Institution of Gas Engineers recommended three processes—the active-carbon, the oil-washing, and the catalytic-for removing sulfur from coal gas. The activecarbon and oil-washing processes are now in use at 25 plants and the catalytic at 1 plant. Sulfur supplies were conserved by licensing

consumers.13

Italy.—Conflicting reports obscure the Italian sulfur situation. the one hand, it has been said that production in 1940-41 was 7 percent less than in the previous year and that labor and equipment shortages, transportation problems, and loss of export markets have seriously restricted the industry. On the other hand, it is stated that the financial situation of producers was satisfactory and no Government subsidies were required; that 200,000 men are now employed compared with 80,000 in 1938-40; and that all requirements were satisfied without diminishing existing stocks.14 Evidence of some difficulties is found in the organization of a joint German-Italian company, Societa per Incremento Produzione Zolfi, whose stated purpose is to deal with the problems of high costs and lost markets by pooling inventions and introducing a more efficient process.

Japan.—Although exact information is lacking for 1942, it is known that native sulfur deposits in Japan make it self-sufficient in this

commodity.

Mexico.—At present the only sulfur produced in Mexico is a very impure material from the State of San Luis Potosí. A new carbon disulfide plant will use it as a raw material.

Benitez, Fernando, Chile: Eng. and Min. Jour., vol. 143, No. 8, August 1942, p. 78.

Chemical and Engineering News, vol. 20, October 25, 1942, p. 1311.

Wilson, James Parker, Consular Report 290.

Chemical and Metallurgical Engineering, vol. 49, No. 1, January 1942, pp. 159–160.

Chemical and Engineering News, vol. 20, No. 24, December 25, 1942, p. 1655.

Mining Journal (London), vol. 219, No. 5588, September 26, 1942, p. 459.

New Zealand.—Consideration was given to opening deposits in the Hot Lakes district, and research agencies studied the concentration problems involved.

Palestine.—In the Gaza Area a sulfur deposit estimated at 1 million

tons has been reported.15

Spain.—The European press reported that Sociedad Española de Construccion Electromecanica is to operate a new plant capable of producing 50,000 tons of sulfur and 15,000 tons of sulfuric acid annually.

Sweden.—Sulfur is a byproduct of the Swedish Navy's new shale-oil

plant at Kinnekulle. Sulfur supplies are under strict allocation. <sup>16</sup>

U. S. S. R.—Reports continue to appear of the discovery of huge supplies of native sulfur, comparable with the Sicilian deposits, in the Turkmen S. S. R. east of the Caspian Sea.

## **PYRITES**

## DOMESTIC PRODUCTION

In 1942, for the third successive year, a new record was attained in production of pyrites in the United States—12 percent higher than the 1941 total. Ninety-eight percent of the output was classified as fines, largely flotation concentrates, and the remainder as lump.

Pyrites (ores and concentrates) produced in the United States, 1938-42

	Quantity				Qua		
Year	Gross weight (long tons)	Sulfur content (percent)	Value	Year	Gross weight (long tons)	Sulfur content (percent)	Value
1938 1939 1940	555, 629 519, 497 626, 640	39. 4 42. 3 41. 8	\$1, 685, 766 1, 560, 000 1, 920, 000	1941 <sup>1</sup> 1942	645, 257 720, 363	41.9 42.6	\$2,009,000 2,464,000

<sup>1</sup> Revised figures.

都になる あるという

In 1942, 492,720 long tons were consumed by the producing companies and 234,639 tons were sold compared with 443,983 and 207,504 tons, respectively, in 1941.

## REVIEW BY STATES

California.—The Mountain Copper Co. produced pyrites in California in 1942; output came from the Hornet mine in Shasta County.

Colorado.—Four companies reported a total production of 11,067 long tons in 1942. They were Minnesota Mines, Inc., Clear Creek County; Rico Argentine Mining Co., Dolores County; and John Hamm Mining & Milling, Ltd., and Resurrection Mining Co., Lake

Illinois. - From its coal-cleaning plant in Henry County, the Midland Electric Coal Corporation produced 13,562 long tons of pyrite

(coal brasses) in 1942.

Indiana.—The Snow Hill Coal Corporation produced pyrite (coal

brasses) at its Talleydale mine in Vigo County in 1942.

Montana.—The pyrites produced in Montana in 1942 came from the Anaconda Copper Mining Co. at Anaconda, where it is recovered as a flotation concentrate in copper-plant operations.

New York.—In 1942 New York produced 68,826 tons of pyrites.

Chemical Age, vol. 47, No. 1205, August 1, 1942, p. 105.
 Foreign Commerce Weekly, vol. 8, No. 6, August 8, 1942, p. 28.

Pennsylvania.—The Bethlehem Steel Co. produced pyrite concen-

trates in Lebanon County.

Tennessee.—The Tennessee Copper Co. operations in Ducktown Basin, Polk County, made Tennessee the largest producer of pyrites in 1942. None of this material, a flotation concentrate, appeared on the market, as all of it was consumed by the producing company.

Virginia.—The General Chemical Co. produced a substantial tonnage of pyrites at the Gossan mine in Carroll County and consumed

the entire output in its own manufacturing operations.

Wisconsin.—The one company reporting production of pyrites in Wisconsin in 1942 was the Vinegar Hill Zinc Co., Grant County. The company sulfuric acid plant consumed the entire output.

#### FOREIGN TRADE

Compared with 1941, imports of pyrites decreased 19 percent in 1942, largely owing to an 87-percent drop in tonnage from Spain. Increased Canadian shipments, which now occupy the position in the United States market formerly held by Spanish, partly counteracted the loss. Canada furnished 94 percent of the imports in 1942.

Although little or none was available, Spanish pyrites, guaranteed 48 percent sulfur, was quoted nominally at 12 cents per long-ton unit

of sulfur, c. i. f. United States ports.

Pyrites, containing more than 25 percent sulfur, imported into the United States, 1938-42, by countries

	1938		1	939	1	940	1	941	1	942
Country	Long	Value	Long tons	Value	Long tons	Value	Long tons	Value	Long tons	Value
Canada Greece	30,064	\$135,659	176, 804 22, 800	\$470, 336 106, 271	81, 157	\$560, 476	244, 287	\$1, 151, 964	282, 896	\$1, 313, 295
Mexico Spain	202 303, 968			738, 439	203 325, 644	719 790, 172	320 124, 231	1,500 326,052	682 16, 561	
grand the section of	334, 234	846, 164	482, 336	1, 315, 046	407,004	1, 351, 367	368, 838	1, 479, 516	300, 139	1, 360, 156

In 1942 receipts of pyrites in the Philadelphia and Baltimore customs districts sank to 6 percent of the total, and none came into New York. Seventy-five percent entered through the Buffalo district.

Pyrites, containing more than 25 percent sulfur, imported into the United States, 1938-42, by customs districts, in long tons

Customs district	1938	1939	1940	1941	1942
Buffalo	5, 130 113, 838	21, 940 176, 982	80, 076 19, 702	227, 510 24, 231	225, 924 12, 561 82
Michigan Montana and Idaho				12, 569	29, 163 366
New YorkOhio	55, 830	46, 170 2, 000	82, 292	317	1
Philadelphia St. Lawrence	130, 703	189, 727	215, 373	88, 219	6, 102 80
San DiegoSouth Carolina	202 5, 265	4, 396	203	320	732
Vermont Virginia Washington	15, 713 7, 553	31, 433 8, 885 803	937 8, 331 90	3, 889 11, 781 2	15, 439 4, 000 5, 689
	334, 234	482, 336	407, 004	368, 838	300, 139

AND ALLEY

#### WORLD PRODUCTION

Although little or no precise statistical information is available for the wartime period, world production of pyrites in 1942 probably approximated 9 million metric tons containing about 3,900,000 tons of

World production of pyrites (including cupreous pyrites), 1938, 1941, and 1942, by countries, in metric tons 1

[Compiled by B. B. Waldbauer]

	19	38	19	41	1942		
Country 1	Gross weight	Sulfur content	Gross weight	Sulfur content	Gross weight	Sulfur content	
Algeria Australia: Tasmania Canada Cyprus (exports) Czechoslovakia  Finland France Germany Greece Italy Norway Poland Portugal Rumania Southern Rhodesia Spain  Sweden Union of South Africa United Kingdom United Kingdom Uruguay Yugoslavia	44, 150 51, 084 40, 464 523, 574 (1) 102, 979 147, 208 465, 267 244, 000 930, 312 1, 027, 776 92, 209 558, 327 111, 205 27, 2065 27, 277, 003 186, 390 31, 017 4, 351 564, 547 70 150, 402	19, 430 (2) 20, 300 20, 300 256, 551 (7) 44, 281 65, 655 200, 064 118, 605 386, 079 446, 939 36, 883 251, 250 7, 061 10, 900 41, 145, 341 13, 947 (2) 222, 612 (2) 67, 681	(2) (275, 202 (275, 202 (2) (2) (2) (3) (3) (4) (7) (7) (9) (172, 759 (9) (172, 759 (9) (19) (19) (19) (19) (19) (19) (19)	(2) 135, 287 (2) (2) (2) (3) (4) (77, 740 (2) (4) (2) (4) (2) (4) (2) (4) (4) (4) (5) (6) (7) (7) (7) (7) (8) (9) (9) (9) (9) (9) (9) (9) (9) (9) (9	(2) (2) (2) (2) (10,000 (2) (2) (3) (4) (5) (7) (2) (2) (2) (4) (7) (8) (9) (9) (9) (9) (9) (9) (9) (9) (9) (9	(2) (3) (2) (2) (2) (2) (3) (3) (4) (5), 680 (7) (4) (1), 505 (8) (9) (9) (1), 885 (9)	
Estimated world total	10, 000, 000	4, 300, 000	8, 500, 000	3, 700, 000	9, 000, 000	3, 900, 000	

<sup>&</sup>lt;sup>1</sup> In addition to countries listed Belgium, Brazil, China, Chosen, Eire, India, Japan, and U. S. S. R produced pyrites, but production data are not available.

<sup>2</sup> Data not available.

<sup>3</sup> Slovakia only.

Estimated.

January to October, inclusive.

January to July, inclusive January to September, inclusive.
 Rovised figures.

Australia.—Before the war Australian sulfur demand was supplied principally by imported elemental sulfur. As this trade dwindled under the pressure of shipping priorities, attention was given to the possibility of achieving self-sufficiency through pyrite. A pyrite industry already exists on Tasmania. Deposits at Eulaminna near Murrin, the Great Victoria at Burbridge, the Iron King at Norseman, and others at Spargo's Reward and St. Ives were explored.<sup>17</sup> During the latter part of 1942 it was reported that production of pyrite had

Canada.—With Spanish pyrites available only intermittently during 1942, Canadian concentrates enjoyed a very good market in the United States. Aldermac was shipping at the rate of 16,000 tons monthly (12,000 tons from production and the rest from stock). The life of this mine was estimated early in 1942 at 16 months, as the ore body is near exhaustion. 18 Other pyrite-producing mines active in

<sup>6</sup> Average sulfur content of pyrites was 42 percent in 1931, latest year for which such information is available.

Mineral Trade Notes, Confidential Series 10, April 1943, p. 29.
 Northern Miner, vol. 28, No. 15, July 2, 1942, p. 9.

1942 were the Noranda in Quebec and the Britannia in British Colum-Prices on most contracts were 5 cents or better per unit. 19 Development of a property in Delestre Township, Quebec, was proposed by Delandore Iron & Sulphur Mines. Open-pit methods would be used on a deposit reported in 1937 to total 13,500,000 tons, containing 12 percent pyrite, and 88 percent pyrrhotite, which would concentrate to 37.5 percent sulfur and 54.5 percent iron.<sup>20</sup> A proposal was reported to install equipment in the Golden Manitou Mill in Quebec to enable it to recover 130 tons of pyrite per day from its zincgold-silver-pyrite ore.

Cyprus.—Pyrite production in Cyprus has virtually ceased as the

island is in a critical and exposed position in the war zone.21

Eire.—After years of idleness, the pyrite deposits in County Wicklow are supplying sulfuric acid for the production of fertilizer from phosphate deposits in County Clare. The goal is to supply a quarter of Eire's normal consumption of superphosphate.22

Portugal.—During the first 10 months of 1942, 112,624 metric tons

of pyrites were produced in Portugal.23

Spain.—In spite of Spain's enigmatic position in the war, it maintained its pyrites trade with Great Britain and to some extent with the United States. During the first 9 months of 1942, 162,417 metric tons were reported shipped to the United Kingdom through the ports of Huelva and Seville. Only 16,561 tons were exported to the United States in 1942—a mere fraction of the 1938-40 average (300,000 tons a year). American shipments were limited to Spanish ships, and no cargoes moved after September. In general, the evidence seems to agree that 1942 was a poor year for Spanish pyrites, and efforts were made to consume greater quantities within Spain, partly to benefit the industry but more particularly to relieve an acute shortage of arsenic and copper. Conversion of pyrites to more salable products was encouraged, and several plants took steps to install additional equipment for that purpose. The Seville Sulphur Copper Co. was ready to suspend operations owing to low quality and to transportation difficulties.24

Sweden.—Domestic production of pyrites increased as imports declined; but all sulfur supplies were very low, and some industrial

activity was curtailed by the shortage.25

U. S. S. R.—Some reports indicate that in 1938 Russia was one of the leading pyrites producers, with an output approaching 1 million tons, derived chiefly from cupriferous ore bodies in the Urals and from coal mines.26 Details are lacking for 1942, but it is certain that vast quantities of sulfur were required in the development and operation of Russia's large, rapidly expanding industries.

Northern Miner, vol. 28, No. 24, September 3, 1942, p. 17.
Canadian Mining Journal, vol. 63, No. 1, January 1942, p. 62,
Il Iron and Coal Trades Review, vol. 144, No. 3866, April 3, 1942, p. 316,
Chemical Age (London), vols. 46 and 47, Nos. 1196 and 1223, May 30 and December 5, 1942.
Mineral Trade Notes, Confidential Series 9, March 1943, p. 33,
Metal Bulletin (London), No. 2709, July 14, 1942, p. 4.
Mineral Trade Notes, Confidential Series 10, April 1943, p. 38.
Milliams, David, Mineral Resources of U. S. S. R.: South African Min. and Eng. Jour., vol. 53, part 2, No. 2594, October 17, 1942.

# PHOSPHATE ROCK

By BERTRAND L. JOHNSON AND K. G. WARNER

## SUMMARY OUTLINE

	Page		Page
General conditions	1363	Prices	1368
Salient statistics		Review by States	1369
Effects of war on world trade	1364	Foreign trade	1378
Production Sales	1366	World production	1377
Distribution of sales	1367	Technologic developments Superphosphates	1378 1378
Consumption	1368	Basic slag	1379

# GENERAL CONDITIONS

The record for marketed production of phosphate rock made in 1941 was not quite attained in 1942, as the quantity sold or used by producers was 4,644,240 long tons (see fig. 1), about 45,000 tons less




FIGURE 1.—Marketed production of domestic phosphate rock, 1900-1942.

than in 1941. The value, however, was about a million dollars greater than in 1941. Mined production—4,818,938 long tons in 1942—was 2 percent less than the all-time record of 4,922,183 tons in 1941. Exports fell nearly one-half million tons to 528,716 tons, whereas imports, a few thousand tons only, were slightly less than in 1941. Stocks in producers' hands at the end of the year increased 5 percent over 1941. Apparent domestic consumption of phosphate rock in 1942 was much the greatest ever recorded, exceeding 1941 by 12 percent.

of the section of the

General scientific papers published recently include those by Frondel, Dietz, Emery, and Shepherd, McConnell, and de Villiers A paper by Jacob 5 covers the phosphate-rock industry in general.

Salient statistics of the phosphate-rock industry in the United States, 1941-42

		1941			1942	
	Value at mines		Value at mine		mines	
	Long tons	Total	Average	Long tons	Total	Average
Production (mined)	1 4, 922, 183	(²)	(2)	4, 818, 938	(2)	(2)
Sold or used by producers: Florida: Land pebbleSoft rock. Hard rock.	3, 279, 706 47, 750 38, 116	\$9,890,510 132,472 211,049	\$3.02 2.77 5.54	48, 470	\$8, 826, 705 155, 345 396, 527	\$3. 05 3. 20 5. 66
Total Florida Tennessee <sup>§ 4</sup> Idaho Montana Utah Virginia	97, 274 105, 108 1, 340	444, 154	4. 10 4. 57 3. 03	3, 012, 240 1, 366, 335 114, 079 150, 402 1, 184 (4)		3. 11 4. 48 4. 48 3. 81 6. 26 (4)
Total United States	1 4, 689, 652 4, 340 1, 019, 960	1 15, 596, 273 32, 816 5, 738, 859	7.56	4, 644, 240 3, 765 528, 716	16, 597, 492 24, 887 3, 348, 341	6.61
Apparent consumption 7	3, 674, 032			4, 119, 289		
Stocks in producers' hands, Dec. 31: Florida <sup>3</sup> Tennessee <sup>3 8</sup> Other	1, 483, 000 292, 000 3, 000	(2) (2) (2)	(2) (2) (2)	1, 426, 000 437, 000 4, 000	(2) (2) (2)	(2) (2) (2)
Total stocks	1,778,000	(2)	(2)	1, 867, 000	(2)	(2)

<sup>1</sup> Revised figures

<sup>2</sup> Figures not available.

Includes sintered matrix.

Virginia included with Tennessee.

Market value (or price) at port and time of exportation to the United States.

Value at port of exportation.

Value at put of exportant.
 Quantity sold or used by producers plus imports minus exports.
 Includes brown-rock matrix of sinter grade and sintered brown rock in 1941 and 1942 and blue rock in 1942.

Effects of war on world trade.—Before the onset of World War II international trade in phosphate rock was well established in certain definite channels; this commodity moved largely from three major producing centers-North Africa, the United States, and Oceania-to three principal consuming areas—Europe, Japan, and Australia and New Zealand. Two of the producing areas—North Africa and Oceania—exported virtually all of their production; that from North Africa went principally to Europe, but some was sent to Japan; and that from Oceania was split between Japan and the British Dominions Australia and New Zealand. The other important producing area, the United States, shipped only its surplus (about a third of its pro-This went chiefly to Europe and Japan. Of the various consuming areas, Europe depended almost entirely upon imports, as did also Australia and New Zealand. Japan depended largely upon foreign sources, whereas the United States alone was entirely independent in respect to external supplies.

I Frondel, Clifford, Mineralogy of the Calcium Phosphates in Insular Phosphate Rock: Am. Mineral., vol. 28, No. 4, April 1943, pp. 215-232.

Dietz, R. S., Emery, K. O., and Shepherd, F. P., Phosphorite Deposits on the Sea Floor off Southern California: Bull, Geol. Soc. America, vol. 53, 1942, pp. 815-848.

McConnell, Duncan, Griphite, a Hydrophosphate Garnetoid: Am. Mineral., vol. 27, 1942, pp. 452-461.

de Villiers, J. E., The Carbonate Apatites; Francolite from the Richtersveld, South Africa: Am. Jour. Sci., vol. 240, 1942, pp. 443-447.

Jacob, K. D., Phosphate Rock (in 1941): Mineral Ind., vol. 50, 1942, pp. 413-433.

These normal world trade relations in phosphate rock have been almost completely upset by the war's developments. Each major development has reacted on international trade in this commodity. The outbreak of the war between the Allied Nations England and France and the German Reich on September 3, 1939, with the consequent British blockade of Germany, brought to a complete stop all exports of American and North African rock to Germany and the territory it controlled in central Europe—Austria, Czechoslovakia, Danzig, and Poland—except those that may have entered through the neutral Mediterranean countries in southeastern Europe.

With the invasion of Norway by Germany in April 1940, phosphaterock shipments to the Scandinavian countries from the United States ceased, and in May 1940 the German invasions of Netherlands and Belgium ended all possibility of further shipments to those countries.

The defeat of France in June 1940 had many repercussions in the world phosphate-rock trade. It stopped the movement to Britain and the Union of South Africa from the North African deposits—normally the principal source of supply for this material—in consequence, Great Britain turned to the United States for supplies, and exports of American rock to Great Britain in 1940 exceeded even the large amount sent from the United States to Japan in that year. Large shipments were also made in 1940 from the United States to the Union of South Africa, which normally obtained its requirements from Morocco. Record shipments went to Canada from the United States, and American rock was sent to Portugal for the first time in many years. As a result of these new demands, exports from America were

maintained at about 70 percent of the pre-war volume.

The entrance of Italy into the war as an Axis partner, following the collapse of France, stopped the shipments of American phosphate rock not only to Italy but also to countries such as Switzerland and Hungary that had been receiving American phosphates through Italian ports. The defeat of France and the entry of Italy into the war also had a very adverse effect on the phosphate industry of the French possessions in North Africa—Algeria, Morocco, and Tunisia—countries that normally produce about 4 million tons of rock a year and export about 3½ million tons to Europe. Shipments from French North Africa in 1940 and exports to Europe in that year are stated to have been only about 50 percent of those of 1939. Shipments were destined chiefly to France, Italy, and Spain. North African shipments moved to Germany through Italian ports. All exports from Tunisia in the latter half of the year and throughout most of 1941 went to Germany and Italy. Owing principally to the stoppage of Italian commerce through the Suez Canal by the British and to a great drop in shipments to Japan, phosphate exports from Egypt, which in 1938 and 1939 had amounted to over 400,000 metric tons a year, decreased to only 77,069 tons in 1940.

On September 20, 1940, Japan invaded Indochina, and 7 days later (September 27, 1940) joined the Berlin-Rome Axis, resulting in the cutting off of shipments of phosphate rock to Japan by Britain from Egypt, Nauru and Ocean Islands, and Christmas Island.

In 1941 two further major interferences in world trade in phosphate rock occurred. The first was the German attack on Soviet Russia in June 1941, which cut off imports of Russian apatite into Germany and initiated movement of the Kola Peninsula apatite from the port of

Murmansk to Britain and the United States. The second was the surprise attack on Pearl Harbor in the Hawaiian Islands on December 7, 1941, which brought the United States into the war on the side of Britain and stopped shipments from the United States to Japan.

Early in 1942 Japan conquered most of the phosphate-producing islands of Oceania (Nauru, Ocean, and Christmas Islands) and became self-sufficient in this commodity, fully compensating for the loss of imports from the United States, Egypt, and French possessions. This move by Japan also largely cut off the supplies to the British Dominions Australia and New Zealand, which had come principally

from Nauru and Ocean Islands.

The world phosphate-trade picture changed again in November 1942 with United Nations occupation of the phosphate-bearing areas of French North Africa in Algeria, Morocco, and Tunisia, and German occupation of the former "unoccupied" portion of France. events stopped the supplies of North African phosphates that had been going to France, Italy, and Germany and cut off the entire continental European market except the neutral coastal countries of Spain and Portugal, throwing the entire North African production on the remaining vastly restricted world markets in Allied and neutral countries in direct competition with American phosphate rock and also raising the possibility of invasion of the American domestic market by the French North African phosphate. The British Isles can now again get their supplies from French North Africa, releasing space on ships traveling from the United States to Britain and possibly eliminating much of the American export trade in this material. Australia and New Zealand-long cut off from their former sources of supply in Nauru and Ocean Islands—and the Union of South Africa can now obtain phosphate rock from North African sources.

Thus, at the beginning of 1943 Japan alone of the Axis Powers is self-sufficient in phosphate rock, whereas the European members have been cut off from the U. S. S. R. and all extra-European sources of supply and are limited to small, controlled European deposits, apparently inadequate for their economy. The United Nations, on the other hand, have at their disposal the great phosphate resources and industries of the United States and French North Africa—a supply far exceeding the needs of both Allied and neutral nations of

the world.

#### PRODUCTION

Phosphate rock was mined in 1942 in Florida, Tennessee, Montana, Idaho, and Utah, and apatite was recovered from an apatite-ilmenite ore in central Virginia. Total mine production declined about 100,000 tons from the all-time record output reached in 1941.

Phosphate rock mined in the United States, 1933-42, by States, in long tons

Year	Florida	Tennes- see <sup>1</sup>	West- ern States	United States	Year	Florida	Tennes- see <sup>1</sup>	West- ern States	United States
1933 1934 1935 1936 1937	2, 039, 531 2, 464, 969 2, 598, 337 2, 645, 819 3, 179, 588	394, 311 493, 501 737, 866	23, 663 38, 958 67, 490 79, 152 139, 670		1938 1939 1940 1941 1942	2, 722, 927 2, 791, 360 2, 782, 956 3, 417, 900 2, 984, 503		139, 040 164, 570 3203, 216	3, 987, 970 4, 068, 077 34, 922, 183

1 Includes small quantity of apatite from Virginia.

<sup>2</sup> Revised figures.

<sup>&</sup>lt;sup>2</sup> Includes also small quantity of phosphate rock from South Carolina,

#### SALES

For the third consecutive year in this decade the quantity of domestic phosphate rock sold or used by producers exceeded 4 million tons. 1942 the phosphate rock sold or used was about 45,000 long tons less than the all-time record figure of 1941. Although its value was more than a million dollars greater than in 1941, it was still far below the record value of the boom year 1920.

Phosphate rock sold or used by producers in the United States, 1938-42

		Value a	t mines			Value at	mines	
Year	Long tons	Total	Average	Year	Long tons	Total	Average	
1938 1939 1940	3, 739, 238 3, 757, 067 4, 002, 700	\$12, 952, 143 12, 294, 042 12, 334, 662	\$3. 46 3. 27 3. 08	1941 <sup>1</sup> 1942	4, 689, 652 4, 644, 240	\$15, 596, 273 16, 597, 492	\$3. 33 3. 57	

<sup>1</sup> Revised figures.

## DISTRIBUTION OF SALES

Two distinct groups appear in the shipments of domestic phosphate rock by grades in recent years; one contains all phosphate rock of less than 60 percent B. P. L. (bone phosphate of lime) and the other all grades of 68 percent B. P. L. and higher. Both groups are increasing in size, and the gap between them is more distinct.

Seventy percent of the domestic phosphate rock sold or used by producers in 1942 is reported to have gone into the manufacture of superphosphates, and the quantity so consumed was over 400,000 tons greater than in 1941.

Phosphate rock sold or used by producers in the United States, 1941-42, by grades

		1941			1942	
	Quan	tity		Quar	tity	
	Long tons	Percent of total	Value	Long tons	Percent of total	Value
Grades—B. P. L. content (percent):						
Below 60 60 to 66 68 basis, 66 minimum	428, 869 3 10, 968 232, 540	(4) 9 5	(2) (2) (2)	477, 916 1, 412 373, 329	(4)	(2)
70 minimum 72 minimum	408, 454 1, 524, 476	9 32	(2)	198, 820 1, 686, 312	8 4 37	(2) (2) (2) (2) (2)
75 basis, 74 minimum 75 minimum 77 basis, 76 minimum	1,065,272	23 13	(2) (2)	736, 797	16	(2)
77 minimum Above 85 (apatite) Undistributed 5	} 411,593	9	(2)	559, 111 610, 543	12 13	(2) (2)
	3 4, 689, 652	100	3\$L5, 596, 273	4, 644, 240	100	\$16, 597, 492
Uses: Domestic:						
Superphosphates Phosphates, phosphoric acid, phosphorus, ferrophos-	2, 825, 456	60	(2)	3, 242, 689	70	(2)
phorus Direct application to soil Fertilizer filler	644, 948 143, 196	14 3	(B)	649, 816 184, 233	14 4	(2) (2)
Stock and poultry feed	31, 381 3, 771 5, 492 1, 035, 408	(4) (4) 22	(2) (2) (2) (2) (2) 4, 448, 298	30, 116 8, 466 6, 146 522, 774	(f) (f) 11	(2) (2) (2) (2) (2) 2, 354, 019
	<sup>3</sup> 4, 689, 652	100	<sup>3</sup> 15, 596, 273	4, 644, 240	100	16, 597, 492

<sup>1</sup> Bone phosphate of lime. 2 Figures not available. 3 Revised figures. 4 Less than 0.5 percent.


8 Includes grades of B. P. L. content 65, 68/69, between 69 and 72.9, 72-73, 73, 73.2, 76, 76.9, 78, and above
85 percent; also ground phosphate rock and dust, B. P. L. content not known.

9 Includes some calcined phosphate and phosphatic material used in pig-iron blast furnaces, construction work, filter bed, parting compounds, research, refractories, in manufacture of concentrated fertilizers, and in minor uses not specified.

7 As reported to Bureau of Mines by domestic producers.

## CONSUMPTION

The annual consumption of phosphate rock in the United States from 1867 to 1942 is shown in figure 2. The effect of World War II upon the domestic consumption of phosphate rock is well-shown by the abnormal extension of the line showing consumption above



- FIGURE 2.—Consumption of phosphate rock in the United States, 1867-1942.

the logistic curve indicative of the normal average demand. The apparent consumption in 1942 was 4,119,289 long tons, much the highest ever recorded.

## **PRICES**

Trade-journal (Oil, Paint and Drug Reporter) quotations for the various grades of phosphate rock changed little during the first 10 months of the year. Maximum prices on Florida land-pebble phosphate rock and Tennessee brown-rock phosphate were established by the Office of Price Administration in a new schedule issued October 13, 1942, and effective October 19, 1942 (Maximum Price Regulation 240).

Prices per long ton of Florida and Tennessee phosphate rock, bulk f. o. b. mine, in

[Leaders indicate that prices are not quoted]

	Jan. 5– Feb. 23	Mar. 2- June 29	July 6- Sept. 28	Oct. 5- Oct. 12	Oct. 19- Dec. 28
Florida: High-grade hard rock: Grades—B. P. L. <sup>3</sup> content (percent): 77-76.	\$5.00	\$5.00			
Land pebble: Grades—B. P. L. <sup>2</sup> content (percent): 68-66	2.00 2.40 3.00 4.00	2.20 2.70 3.20 4.00	\$2. 20 2. 70 3. 20 4. 00	\$2. 20 2. 70 3. 20 4. 00	\$2.00 2.49 3.00 4.00
Tennessee: Grades -B. P. L. content (percent): 72-70	5.00				5. 00 5. 30
75-74 68-66 70 minimum 72 minimum 60-66	6.00	6. 50 4. 50 5. 00 5. 50	5.00 5.50 4.50	6. 50 4. 50 5. 00 5. 50	4. 30
70-68			4. 00		4. 80

<sup>1</sup> Weekly quotations of Oil, Paint and Drug Reporter.

Near the close of the fiscal year ended June 30, 1942, the Office of Price Administration made plans for the Federal Trade Commission to study costs, prices, and profits in the fertilizer and related products industry. The inquiry began with a study of 11 important companies in the phosphate rock-mining industry.6

## REVIEW BY STATES

Florida.—Another set-back to the growth of the Florida phosphaterock industry occurred in 1942 (see fig. 3). The quantity of phosphate rock sold or used by producers in Florida—3,012,240 long tons—was 353,332 tons less than the 1941 sales; and, although the average value per ton increased from \$3.04 to \$3.11, the total value of the shipments was \$855,454 less. The decrease was due to the greatly lessened foreign demand for Florida land pebble. The average values per ton for all types were higher in 1942. Sales of hard rock nearly doubled those of 1941, but the increase in sales of soft rock was slight.

Hard-rock-phosphate mining operations were conducted jointly by C. & J. Camp, Inc., and J. Buttgenbach & Co. in sec. 22, Citrus County, 3 miles from Hernando. The other hard-rock-phosphate company the Dunnellon Phosphate Mining Co.—did no mining in 1942 but shipped hard rock from stocks. The Pembroke Chemical Corporation reported its sintering operations as permanently inactive, but this company together with the usual land-pebble producers mined and shipped land pebble.

Stocks of Florida phosphate rock reported by producers December 31, 1942, were 57,000 tons less than at the end of 1941 but still totaled 1,426,000 tons.

Federal Trade Commission, Annual Report for the Fiscal Year Ended June 30, 1942: 1942, 136 pp.; see

<sup>556250-43-</sup>




FIGURE 3.—Rate of growth of phosphate rock sold or used by producers, by States, 1933-42.

Florida phosphate rock sold or used by producers, 1938-42, by kinds

		Hard rock Soft				oft rock 1	
Year	Value at mines		mines	Value at mine		mines	
iear	Long tons	Total	Average	Long tons	Total	Average	
1938 1939 1940 1941 1941	125, 048 89, 096 22, 367 38, 116 70, 014	\$601, 922 411, 455 100, 353 211, 049 396, 527	\$4.81 4.62 4.49 5.54 5.66	53, 479 41, 906 41, 845 47, 750 48, 470	\$178, 093 128, 435 102, 508 132, 472 155, 345	\$3. 33 3. 06 2. 45 2. 77 3. 20	

	1	and pebble			Total	
Year		Value at mines		Long tons	Value at mines	
	Long tons	Total	Average	Total	Average	
1938 1939 1940 1941	2 2, 528, 808 2 2, 547, 782 2 2, 780, 800 3, 279, 706 2, 893, 756	2 \$7, 993, 665 2 7, 353, 567 2 7, 538, 316 9, 890, 510 8, 826, 705	\$3. 16 2. 89 2. 71 3. 02 3. 05	2 2, 707, 335 2 2, 678, 784 2 2, 845, 012 3, 365, 572 3, 012, 240	2\$8, 773, 680 2 7, 893, 457 2 7, 741, 177 10, 234, 031 9, 378, 577	\$3. 24 2. 95 2. 72 3. 04 3. 11

<sup>1</sup> Includes material from waste-pond operations.

Mansfield <sup>7</sup> presents the results of a detailed study of the phosphate reserves of Florida. Total reserves are placed at 5,081,839,000 long tons, of which 2,058,583,000 are classified as known, 1,227,146,000 tons as probable, and 1,796,110,000 tons as possible. Reserves better than 74 percent B. P. L. total only 130,000,000 tons. Over two-thirds of the reserves are in the land-pebble and nearly one-third

<sup>&</sup>lt;sup>2</sup> Includes sintered matrix.

<sup>&</sup>lt;sup>7</sup> Mansfield, G. R., Phosphate Resources of Florida: Geol. Survey Bull. 934, 1942, 82 pp.

in the hard-rock field. The phosphate rock resources of the Hawthorn formation and the Caloosahatchee marl are not included. Taylor 8 in the fourth article of a series describes some of the current

practices in the field of land-pebble phosphate rock.

The International Minerals & Chemical Corporation completed in June 1942 its new Peace Valley mine, washer, and flotation plant, about a mile from Pembroke, on land leased from the Pembroke Chemical Co. Production began July 1, 1942. The output of this operation is sent to International's central drying and grinding plant at Mulberry, the drying capacity of which has recently been increased about 60 percent by the addition of a new 7- by 80-foot oil-fired rotary drier. Detailed descriptions of the Peace Valley Plant have been published. The International Minerals & Chemical Corporation sold to Minerals Separation North American Corporation its half interest in the Phosphate Recovery Corporation, which the two companies had developed since 1928. It is also reported to have bought from the Phosphate Recovery Corporation the flotation plants serving its own phosphate mines.

Edwards 10 discusses in detail the electrical equipment of the completely electrified mines and plants of the International Minerals & Chemical Corporation in the Florida land-pebble-phosphate field

and problems of maintenance of this equipment.

The process of separating phosphate by flotation on moving conveyor belts, in use in the land-pebble field at the Hopewell washer (6 miles from Coronet) by the Coronet Phosphate Co., is described in detail in a recent article. Published descriptions also appeared of the froth-flotation and table-concentration plant of the Phosphate Mining Co. in the land-pebble field 12 and the new drying plant of

the American Cyanamid Co. 13

Tennessee.—The tonnage of phosphate rock sold or used by Tennessee producers in 1942 (plus a small quantity of apatite from Virginia) continued the upward trend of recent years (see fig. 3) and exceeded the all-time high of 1941 by 22 percent. The total value of the shipments likewise made a new high record, exceeding the previous record of 1920 (\$4,857,399) by over a million and a quarter dollars. The greater part of the shipments were of brown rock, although a small quantity of blue rock drawn from stocks was used in research work by the Tennessee Valley Authority. Total stocks in hands of producers—brown rock and blue rock—at the close of 1942 were 437,000 long tons, an increase of 50 percent over the stocks on hand December 31, 1941.

<sup>\*</sup> Taylor, W. H., Land-Pebble Phosphate Deposits of Florida—IV: Pit and Quarry, vol. 35, No. 5, No vember 1942, pp. 61-65.

\* Hubbell, A. H., International's New Phosphate Mine and Recovery Plant in the Florida Pebble Field Eng. and Min. Jour., vol. 143, No. 9, September 1942, pp. 43-48.

Pit and Quarry, Phosphate, Barites, and Other Minerals Felt Stimulus of War Demand in 1942: Vol. 35, No. 7, January 1943, pp. 95-97.

\*\*Bedwards, J. H., Metering a Factor in International Minerals & Chemical Corporation's Phosphate Operations: Eng. and Min. Jour., vol. 143, No. 6, June 1942, pp. 43-46.

\*\*Hubbell, A. H., Phosphate Washer Reject Successfully Concentrated on Moving Conveyor Belt: Eng. and Min. Jour., vol. 143, No. 12, December 1942, pp. 51-54.

\*\*Pit and Quarry, Flotation Plant in Florida Recovers Phosphate from Accumulated Tailings: Vol. 35, No. 11, May 1943, pp. 59-62.

\*\*In Pit and Quarry, Fuel, Power, and Labor Costs Decline as New Drying Plant Goes in Service: Vol. 35, No. 3, September 1942, pp. 53-54, 57; Phosphate, Barites, and Other Minerals Felt Stimulus of War Demand in 1942: Vol. 35, No. 7, January 1943, pp. 95-97.

Tennessee phosphate rock (including sintered matrix) sold or used by producers, 1938-42

	Virginia]

	Long	Value a	t mines		Long	Value at	mines
Year	tons	Total	Average	Year	tons	Total	Average
1938 1939 <sup>1</sup>	899, 298 938, 448 994, 361	\$3, 725, 601 3, 856, 505 3, 967, 043	\$4. 14 4. 11 3. 99	1941 1942	1, 120, 358 1, 366, 335	\$4, 590, 965 6, 127, 792	\$4. 10 4. 48

1 Separate figures for brown rock and blue rock cannot be given without disclosing confidential data regarding blue-rock production.

A few private companies and the Tennessee Valley Authority mined phosphate rock in Tennessee in 1942. The private companies include the Armour Fertilizer Works, Charleston Mining Co., Federal Chemical Co., Gilbreath & Pressnell, Harsh Phosphate Co., Hoover & Mason Phosphate Co., International Minerals & Chemical Corporation, Monsanto Chemical Co., and the Virginia-Carolina Chemical Corporation. The Charleston Mining Co., in operation during the first half of 1942, was dissolved and merged June 30, 1942, with its parent company, the Virginia-Carolina Chemical Corporation, which continued mining in Tennessee after the merger. Most of the brown-rock mining in this district is from surface operations.

The International Minerals & Chemical Corporation purchased additional phosphate-rock reserves in the Tennessee field in the fiscal year ended June 30, 1942, according to its annual report, and made further improvements in its mines and plants. Operating practices at this company's plants and at the remodeled phosphaterock plant of the Virginia-Carolina Chemical Corporation were

described in a recent article.14

The improvements at the plant of the Hoover & Mason Co. at Mount Pleasant have been described in recent articles. 15 A phosphate-rock grinding plant erected in 1942 on Swan Creek in Hick-

man County is said to have been operated only a short time.

In 1942 the Tennessee Valley Authority continued <sup>16</sup> its production of elemental phosphorus and phosphatic fertilizers. A plant formerly used for the production of phosphorus-carrying plant foods was enlarged and equipped to produce elemental phosphorus for the Chemical Warfare Service, and large quantities of that element were shipped for munitions manufacture. In June 1942 the Authority had one-fourth of the Nation's capacity for the production of munitions-grade phosphorus. Fertilizer production was continued to the extent that facilities were not needed for elemental phosphorus. The Authority sent about four-fifths of its production of triple superphosphate and calcium metaphosphate fertilizers to United Nations under lend-lease arrangement. The one-fifth reserved for domestic consumption was used in continuing cooperation with State agricultural extension services in a program of tests and demonstrations.

<sup>14</sup> Engineering and Mining Journal, Tennessee Phosphate Field Sees Changes: Vol. 144, No. 3, March

<sup>1943,</sup> pp. 68-71.

1 Engineering and Mining Journal, Tennessee Phosphate Field Sees Changes: II. The Hoover & Mason Company Improves Its Washer in Mount Pleasant District: Vol. 144, No. 4, April 1943, pp. 79-80. Nordberg, Bror, Eliminating Phosphate Wastes: Rock Products, vol. 46, No. 5, May 1943, pp. 48-51, 61.

14 Office of War Information, Tennessee Valley Authority: Advance Release OWI-1043 for Friday aftergoon, January 1, 1943, mim., 5 pp.

Construction of the Tennessee Valley Authority field phosphate plant in Maury County, Tenn., was completed, and the plant was put into operation during the summer of 1942. At the end of the year, approximately 500 tons of phosphate rock were mined a day, and the production of sinter amounted to about 190 tons daily. Phosphate mining, washing, and concentrating operations are carried out on the Authority's phosphate tract, about 5 miles from Columbia, Tenn., near Duck River. The plant at the phosphate tract consists of pit-mining equipment, a washer, water-pumping equipment, a hydroseparator, and auxiliary equipment. The phosphate sands from this plant are pumped approximately 3 miles to the classifying and finishing plant adjacent to the railroad at Godwin, Tenn. The Godwin plant consists of a rake classifier, bowl classifier, hydroseparator, Bird classifier, Dwight-Lloyd sintering machine, drier, and auxiliary equipment.

The Authority prospected nine farms covering 1,827 acres in 1942 and acquired options to purchase mineral rights on seven properties containing 1,117 acres. An option to purchase, in fee simple, a 141-

acre tract in Williamson County was exercised.

Virginia.—Mining was continued at the Piney River nelsonite deposit in 1942 by the Southern Mineral Products Corporation, subsidiary of the Vanadium Corporation of America. The apatite-ilmenite ore (nelsonite) from the open pit was treated in its nearby

mill, with separation of the apatite and ilmenite.

Western States.—Production of phosphate rock in the Western States has been increasing steadily in recent years. The quantity sold or used annually has about doubled in the last 5 years, reaching a record total of 265,665 long tons in 1942 (see fig. 3), with a value exceeding a million dollars for the first time. The production in 1942 came from

Idaho, Montana, and Utah, as in 1941.

Idaho rock sold or used reached a new high in 1942 (114,079 long tons). Two companies were active in this State in 1942. Much the larger was the long-established producer—the Anaconda Copper Mining Co.—which operated its No. 3 mine at Conda, Caribou County. These operations have been described in considerable detail. The other company in Idaho, the Teton Phosphate Co., Boise, shipped phosphate rock from Montpelier in February 1942

from its holdings near that place.

Montana was the largest producer of the Western States group in both 1941 and 1942 (see fig. 4). Its sales have increased sharply in recent years—from 44,384 long tons in 1939 to a new high record of 150,402 tons in 1942. In 1942 Montana had three producers. The largest—the Montana Phosphate Products Co. of Trail, British Columbia—operated the Anderson mine and several Federal leases in Powell County; it exported most of the mined phosphate rock to the Consolidated Mining & Smelting Co. of Canada at Trail. The other producers were the Mineral Hill Mining Co., Butte, Mont., which mined and shipped from its mine near Avon, Powell County, and L. H. Skeels, who shipped a small quantity from Maxville. The Northwestern Improvement Co., St. Paul, Minn., former lessee from the United States (Great Falls Serial No. 077838), conducted no mining operations thereunder in 1942 and on July 1 of that year assigned

<sup>17</sup> Mining World, Conda Operations of the ACM Company; Vol. 4, No. 10, October 1942, pp. 3-8.

the lease to the International Minerals & Chemical Corporation (formerly the International Agricultural Corporation). No production or shipments in 1942 were made by this company from the newly acquired property.

In Utah the Garfield Chemical & Mfg. Corporation mined and shipped phosphate rock from Federal-leased land near Spanish Fork, Utah County, in 1942, for use in pig-iron blast furnaces. During the year revised estimates of the phosphate reserves of Utah were published.<sup>18</sup>

On August 27, 1942, all deposits of vanadium and all public lands containing such deposits owned by the United States in Bannock.




FIGURE 4.—Idaho and Montana phosphate rock sold or used by producers, 1933-42.

Bear Lake, Bingham, Bonneville, and Caribou Counties, Idaho; Rich County, Utah; and Lincoln, Sublette, and Teton Counties, Wyo., were withdrawn (Public Land Order 35, Abe Fortas, Acting Secretary of the Interior) from all forms of appropriation under the public-land laws of the United States, including the mining laws, and from leasing under the provisions of the mineral leasing laws relating to phosphate deposits and were reserved under the jurisdiction of the Secretary of the Interior for use in connection with prosecution of the war. The total area withdrawn, including both public and non-public lands, aggregated approximately 332,300 acres.

<sup>18</sup> Williams, J. S., and Hanson, A. M., Phosphate Reserves of Utah: Utah Agric. Exp. Sta. Bull. 304, 1942, 24 pp.

Western States phosphate rock sold or used by producers, 1938-42

		Idaho		Montana			
Year		Value at	mines		Value at mines		
	Long tons	Total	Average	Long tons	Total	Average	
1938	66, 014 95, 451 99, 088 97, 274 114, 079	\$296, 595 431, 938 441, 598 444, 154 511, 249	\$4. 49 4. 53 4. 46 4. 57 4. 48	66, 491 44, 384 64, 239 105, 108 150, 402	\$155, 917 112, 142 184, 844 318, 588 572, 464	\$2. 34 2. 53 2. 88 3. 03 3. 81	
		Utah			Total		
Year	Long tons	Value at	mines	Tongtong	Value at	mines	
	Long tons	Total	Average	Long tons	Total	Average	
1938 1939 1940 1941 1942	1, 340 1, 184	\$8, 535 7, 410	\$6. 37 6. 26	132, 505 139, 835 163, 327 1 203, 722 265, 665	\$452, 512 544, 080 626, 442 1 771, 277 1, 091, 123	\$3. 42 3. 89 3. 84 1 3. 79 4. 11	

<sup>1</sup> Revised figures.

## FOREIGN TRADE 19

Imports.—Combined imports of apatite and phosphate rock in 1942 totaled 3,765 long tons compared with 4,340 tons (phosphate rock) in 1941. Although no apatite was imported in 1941, in April 1942 a considerable quantity, 920 long tons, was received from the U. S. S. R. Apparently part of this has been included under "Phosphates, crude, not elsewhere specified" in the accompanying table. In May 1942 2,800 long tons of Curação phosphate rock were imported.

Phosphate rock and phosphatic fertilizers imported for consumption in the United States, 1938-42

	1938		1939		1940		1941		1942	
Fertilizer	Long tons	Value	Long tons	Value	Long tons	Value	Long tons	Value	Long tons	Value
ApatitePhosphates, crude, not	2	\$5							179	\$1,025
elsewhere specified	7, 004	80, 534	3, 500	<b>\$23,</b> 625	2, 953	\$19, 536	4, 340	\$32, 816	3, 586	23, 862
used as fertilizer Bone dust, or animal carbon, and bone ash.	29, 028	1, 286, 935	34, 995	1, 627, 608	44, 782	1, 959, 900	55 <b>, 43</b> 0	2, 483, 756	25, 521	1, 150, 319
fit only for fertilizing.	19, 581 15, 199	393, 808 717, 817		799, 179 211, 941	27, 676 785		27, 607 15, 394		7, 855 3, 128	213, 970 159, 799
Slag, basic, ground or unground Precipitated bone, ferti-	691	9, 547	405	5, 168	452	4, 766			894	1, 011
lizer grade	3, 385	98, 725	2, 314	68, 611	1, 141	38, 225			23	85

Exports.—The export trade of the United States in phosphate rock has reacted to the vicissitudes of the present World War. Not only is it much smaller than normal, but the domestic rock is no longer shipped to widely scattered parts of the world. Exports are restricted almost entirely to Canada and the United Kingdom.

<sup>&</sup>lt;sup>19</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

## Phosphate rock 1 exported from the United States, 1938-42

		Val	ue			Val	ue
Year	Long tons	Total	Average	Year	Long tons	Total	Average
1938 1939 1940	1, 140, 841 949, 006 751, 495	\$6, 637, 638 5, 233, 104 3, 845, 495	\$5. 82 5. 51 5. 12	1941 1942	1, 019, 960 528, 716	\$5, 738, 859 3, 348, 341	\$5, 63 6, 33

<sup>&</sup>lt;sup>1</sup> 1938-40: Excludes sintered matrix, which is included under "Other phosphate materials." Excludes 'Phosphate rock: Florida: Other (including soft rock, colloidal and sintered matrix)," included under "Other phosphate materials." 1941-42: which is

## Phosphate rock 1 exported from the United States, 1938-42, by countries HIGH-GRADE HARD ROCK

	19	938	19	39	1	940	19	41	1	942
Country	Long tons	Value	Long tons	Value	Long tons	Value	Long tons	Value	Long tons	Value
D.1	4,000	\$28,000					•			See Maria
Belgium Brazil	4,000	\$20, 000					201	\$3,500		
British Malaya	507	5,000	1,200	\$12,000						
Canada	67, 134	406, 463	45, 162	276, 372	64, 542 22	\$394, 576 210		667, 324	157, 135	\$966, 670
CubaGermany 2	57, 250	369, 787	55 246	345, 290		210				
Italy	3,000	18, 750								
Netherlands	14, 450	94, 420								
Panama	2,900	48 18, 125			673	3, 365				
Poland and Danzig 3 Portugal	2,900	10, 120		5.25 - 12	8. 990	60, 673				
Sweden	32, 675	219, 425	14, 625	102, 375						
United Kingdom 3								285, 062	80, 456	499, 521
	181, 920	1, 160, 018	132, 983	840, 725	84, 592	531, 449	156, 613	955, 886	237, 591	1, 466, 191

#### LAND PEBBLE

· <u></u>										
	1	938	1	939	19	940	19	941	1	942
Country	Long tons	Value	Long tons	Value	Long tons	Value	Long tons	Value	Long tons	Value
Austria Belgium	5, 781 96, 073		36, 729	\$221, 107						
Belgian Congo Canada Czechoslovakia <sup>2</sup>	59, 275 26, 238	155, 987	2,498			\$28, 000 440, 346	103, 827	\$800, 951	97, 951	\$909, 986
Denmark Germany 2 Hungary 2	7. 495 358, 077 10, 017	2, 181, 869	271,801	1, 623, 330 15, 750	5, 261					
Ireland Italy Japan	49, 911 159, 270		86, 375 229, 404	562, 533 888, 598	6, 200 33, 315 218, 456		72, 722	274, 981		
Liberia Mexico Netherlands	39 103, 666		27, 517	178, 283			28	288		
Nigeria Norway Poland and Dan-					1,500 2,001	12,000 15,007				
zig 2 Portugal Sweden	2, 993 66, 113	412, 948			24,837		32, 490	187, 866		
Switzerland Union of South Africa	6,620				51, 311	282, 211	55, 345	314, 658	3, 299	18, 969
United Kingdom 3. Yugoslavia			3,003	20, 270	3,002	19, 513		3, 204, 229		
	1958, 921	15, 477, 620	816.023	4, 392, 379	1666, 903	3, 314, 046	1863, 347	14. 782. 973	1291, 125	1. 882. 150

<sup>1938-40:</sup> Excludes sintered matrix, which is included under "Other phosphate materials." 1941-42: Excludes "Phosphate rock: Florida: Other (including soft rock, colloidal and sintered matrix)," which is included under "Other phosphate materials." sincluded under "Other phosphate materials." which is included under "Other phosphate materials." For statistical purposes, trade with the Sudeten area, as far as ascertainable, is included with Germany while trade with the other Czechoslovak Provinces occupied by Germany, Hungary, and Poland has been included with these countries, since March 18 or 19, 1939. After November 16, 1939, trade with Danzig and that part of Poland occupied by Germany has been included with Germany, and trade with that part of Poland occupied by Germany has been included with U. S. S. R. has been included with U. S. S. R.

Other phosphate materials 1 exported from the United States, 1938-42

Year	Long tons	Value	Year	Long tons	Value
1938	32, 581 29, 080	\$208, 550 192, 306	1941 1942	22, 988	\$262, 045 285, 869
1940	11, 924	201, 047	1942	5, 192	285, 809

<sup>&</sup>lt;sup>1</sup> Includes bone ash, dust, and meal; animal carbon for fertilizer; basic slag; sintered matrix, etc.

High-grade hard-rock phosphate 1 exported from the United States, 1941-42, by customs districts

Customs district	194	1	19	42
Customs district	Long tons	Value	Long tons	Value
Buffalo	255	\$3,016		
Oakota	ii	147	81	\$1,02
Florida	45, 754	285, 062	80, 273	497, 08
Michigan	306	2, 116	815	9,05
Montana and Idaho	88, 960	534, 042	152, 224	913, 26
Ohio Philadelphia	1, 401 201	9, 413 3, 500		
t. Lawrence	201	ə, 500 33	183	2, 44
ermont	244	2,859	100	<b>7</b> •
Vashington	19, 479	115, 698	4,015	43, 32
ustrium (17 m.) – kurtur 18 m.) Halings (18 m.) – kurtur 18 m.) – kurtur 18 m. – kurtur 18 m.)	156, 613	955, 886	237, 591	1, 466, 19

<sup>1</sup> Includes Florida high-grade hard rock, Tennessee and Idaho and Montana phosphate rock.

## WORLD PRODUCTION

Few figures are yet available on phosphate-rock production in foreign countries during 1942.

World production of phosphate rock, 1938-42, by countries, in metric tons <sup>1</sup> [Compiled by B. B. Waldbauer]

Country 1	1938	1939	1940	1941	1942
Algeria Angaur Island (exports) Australia:		<sup>2</sup> 450, 000 ( <sup>3</sup> )	(3)	(9)	8
New South Wales South Australia Western Australia	254	(3)	(3) (3) 40	(3) 8, 597 (3)	8
Canada Chile (apatite)	189	(3) 142 9, 014	(3) 325 32,000	(3) (3) 2,256 (3)	(3) (3) 1,716 (9)
China <sup>2</sup> Christmas Island, Straits Settlements (exports). Egypt. Estonia.	8,000 162,425	8,000 177,972 547,538	(3) 241, 826 183, 182 (3)	(3) (3) (3) 111, 708	
Germany India, British Indochina Italy	3, 221 23	(3) (3) 185 35, 694	(3) (3) 22, 266	(a)	(a) (b)
Makatea Island (exports)	5, 699 102, 941	(*) 4 6, 600 160, 680 1, 491, 754	(3) 495 173, 177 (3)	999	0000
Morocco, French (shipments) <sup>6</sup>	33, 113 99, 283	1, 244, 170 18, 777 64, 072	1, 263, 385 34, 085 6, 047	(3) (3) 111, 995	99
New Caledonia	5,000 970 21,703	(3) (3) 23, 545	(3) (3) 14, 613	000	00000000
South-West Africa Spain Sweden (apatite) Tanganyika Territory	23, 429 6, 192	(3) 6, 267 132	(3)		l M
U. S. S. R. (apatite) United States (sold or used by producers)	1, 934, 200 (3) 3, 799, 253	1, 608, 045 (3) 3, 817, 368	(3) (3) 4, 066, 943	2 720,000 2 2,000,000 7 4,764,921	(3) 4, 718, 78
	11,800,000	<sup>8</sup> 11, 500, 000	19, 800, 000	(3)	(3)

<sup>&</sup>lt;sup>1</sup> In addition to the countries listed, Austria, Belgium, France, Japan, Philippine Islands, Poland, and Paiwan produce phosphate rock, but data of output are not available.

<sup>2</sup> Estimated.

<sup>3</sup> Data not available. Estimate included in the total for 1938–40.

<sup>4</sup> Exports.

<sup>4</sup> Exports.

<sup>5</sup> Exports.

<sup>6</sup> Exports during fiscal year ended June 30 of year stated.

<sup>7</sup> Revised.

<sup>8</sup> Partly estimated.

## TECHNOLOGIC DEVELOPMENTS

Several papers 20 on various phases of phosphate-rock technology, in addition to those mentioned in other parts of this chapter, have appeared in recent months.

## SUPERPHOSPHATES

The following table gives the outstanding features of the superphosphate industry in the United States from 1940 to 1942:

Salient statistics of the superphosphate industry in the United States, 1940–42

				1940	1941	1942
Production 1Shipments,1 total			short tons do	3, 898, 641 2, 934, 336	4, 326, 402 3, 633, 871	5, 144, 484 3, 961, 362
To mixers To other acidulator To all others (include Stocks in manufacturers	ling Governi	nent agend	ansfers)do	1, 530, 474 471, 855 932, 007 1, 142, 585	1, 638, 026 659, 514 1, 336, 331 932, 683	1, 916, 772 541, 225 1, 503, 365 973, 224
Exports of superphosph Imports of superphosph Sales of phosphate rock	ates 2 ates 2	-L	long tons do	141, 289 10, 017	146, 875 17, 368	165, 092 16, 659
	<u> Talumuy</u>			2, 564, 844	2, 825, 456	3, 242, 689

<sup>&</sup>lt;sup>1</sup> Bureau of the Census, Monthly Statistics, Superphosphate Industry, 18 percent available phosphoric

2 Department of Commerce.

Superphosphates (acid phosphates) exported from the United States, 1941-42, by countries

		19	941	1	942
Country	and the second	Long tons	Value	Long tons	Value
Argentina Brazil British Guiana Canada El Salvador Mexico Netherlands Indies United Kingdom <sup>-1</sup> West Indies: British Trinidad and Tobago Other British		1, 042 662 455 23, 283 203 48, 924 232 2, 039 49, 578 10 152 17, 897 36 560 1, 478	\$17, 292 25, 269 29, 682 437, 135 2, 980 16, 152 10, 863 55, 782 1, 526, 857 493 2, 933 257, 344 19, 930 30, 176	2, 679  123 150 64, 626 270 110 80, 536  125 16, 411 62	\$52, 500 11, 014 3, 525 999, 803 6, 004 6, 000 3, 601, 014 1, 625 196, 650
		146, 875	2, 983, 582	165, 092	4, 882, 063

<sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

<sup>&</sup>lt;sup>20</sup> Howatt, D. D., Furnace Treatment of Phosphate Ores: Mine and Quarry Eng., vol. 7, No. 7, July 1942,

Jacobs, M. B., War Gases—Their Identification and Decontamination: New York Interscience Publishers, Inc., 1942, 180 pp.
Zergiebel, C. P., and Lucas, J. W., Phosphorus Furnace Reactions: Trans. Electrochem. Soc., vol. 81, 1942, pp. 439-444.

<sup>1942,</sup> pp. 439-444.

Brown, B. E., and Clark, K. G., An Appraisal of Calcium and Potassium Metaphosphates as Sources of Phosphorus for Crop Plants: Am. Fertilizer, vol. 98, No. 5, February 27, 1943, pp. 10-11, 24, 26, Pole, G. R., and Beinlich, A. W., Jr., New Refractory Compositions Resistant to Molten Rock Phosphate: Jour. Am. Ceram. Soc., vol. 26, No. 1, January 1, 1943, pp. 21-37.

Frass, Foster, and Ralston, O. C., Contact Potential in Electrostatic Separation: Bureau of Mines Rept. of Investigations 3667, 1942, 17 pp.

Bridger, G. L., and Neel, R. M., Phosphatic Fertilizer and Iron from Ferrophosphorus: Paper read before Am. Chem. Soc. Meeting, Buffalo, N. Y., September 7-11, 1942; abs., Chem. and Met. Eng., vol. 49, No. 9, September 1942, p. 213.

Walthall, J. H., and Bridger, G. L., Fertilizer by Fusion of Rock Phosphate with Olivine: Paper read before Am. Chem. Soc. meeting, Buffalo, N. Y., September 7-11, 1942; abs., Chem. and Met. Eng., vol. 49, No. 9, September 1942, pp. 209-210.

Superphosphates (acid phosphates) imported for consumption in the United States, 1940-42, by classes 1

	1	940	1	1941		1942	
Class	Long tons	Value	Long tons	Value	Long tons	Value	
Normal (standard) (not over 25 percent P <sub>2</sub> O <sub>5</sub> content).  Concentrated (treble) (over 25 percent P <sub>2</sub> O <sub>5</sub>	7, 057	\$97, 682	12, 017	\$172,990	5, 965	\$80, 409	
content)	2,864 96	39, 982 1, 951	5, 333 18	133, 835 376	10, 694	300, 34	
	10, 017	139, 615	17, 368	307, 201	16, 659	380, 75	

<sup>1</sup> All from Canada.

Several articles relating to the superphosphate industry have appeared in recent months.<sup>21</sup>

#### BASIC SLAG

No recent figures for the production of basic slag are available. In Great Britain, however, the production is said to have increased substantially during the present war, and this is probably likewise true of some of the Axis-controlled nations. In the United States only a few thousand tons of basic slag are produced annually—in the Birmingham iron district, Alabama—and a few hundred tons is imported a year. Phosphatic slag is produced at the steel furnaces at Sydney, Nova Scotia, and the Canadian Government is investigating its possible agricultural utilization.

<sup>21</sup> Harvey, E. W., and Rohner, L. V., Chemical Properties of Various Commercial Superphosphates Before and After Ammoniation: Am. Fertilizer, vol. 97, No. 8, October 10, 1942, pp. 5-6, 24, 26; paper read before Am. Chem. Soc. meeting, Division of Fertilizer Chemistry, Buffalo, N. Y., September 7, 1942.


MacIntire, W. H., and Hardin, L. J., Stability of Admixed Rock Phosphate in Cured Concentrated Superphosphate: Jour. Assoc. Off. Agric. Chem., vol. 25, 1942, pp. 168-176.

Hardesty, J. O., Adams, J. R., and Ross, W. H., Factors Affecting the Availability of Ammoniated Superphosphates: Paper read before Am. Chem. Soc. meeting, Division of Fertilizer Chemistry, Buffalo, N. Y., September 7-11, 1942; abs. Am. Fertilizer, vol. 97, No. 6, September 12, 1942, p. 10.

Jacob, K. D., Marshall, H. L., Reynolds, D. S., and Tremearne, T. H., Composition and Properties of Superphosphate, Volatilization of Fluorine in Superphosphate Manufacture: Ind. and Eng. Chem., ind. ed., vol. 34, No. 6, June 1942, pp. 122-728.

Brown, B. E., Jacob, K. D., and Reid, F. R., Plant Culture and Nitrification Studies with Sludge-Acid Superphosphate: Am. Fertilizer, vol. 96, No. 7, March 28, 1942, pp. 5-6, 24, 26.

Jacob, K. D., Analysis of the Production of Ordinary Superphosphate in the United States in the Calendar Years 1940 and 1941: Am. Fertilizer, vol. 97, No. 2, July 18, 1942, pp. 5-8, 24, 26; No. 3, August 1, 1942, pp. 8-11, 24, 26: No. 4, August 15, 1942, pp. 10-11, 26, 27; No. 5, August 29, 1942, pp. 9-11, 22, 24, 26.



# TALC, PYROPHYLLITE, AND GROUND SOAPSTONE 1

By BERTRAND L. JOHNSON AND K. G. WARNER

## SUMMARY OUTLINE

	Page		Page
		Prices	1385
Salient statistics	1382	Developments in the industry	1385
Sales	1383	Foreign trade	1387
Markets	1384	World production	1389

#### GENERAL CONDITIONS

Declines in the demand in several industries for tale, pyrophyllite, and ground soapstone depressed both the mined production and the quantity sold and used in 1942 to levels below those of 1941. Sales in 1942 were 387,963 short tons, a 7-percent decrease from 1941;




FIGURE 1.—Sales of domestic talc, pyrophyllite, and ground soapstone, 1933-42.

however, the total value of sales—\$4,754,076—was the highest on record. (See fig. 1.) Sales of crude, sawed and manufactured, and ground all decreased in quantity, but only the crude is reported to have decreased in value. All classes of imports were less in quantity and, with the exception of the crude, lower in value. Exports declined both in quantity and value.

Pyrophyllite is included with talc in this discussion because it resembles talc in certain physical properties and is interchangeable

<sup>1</sup> Soapstone sold in slabs or blocks is included in the chapter on Stone.

with talc in some uses, although during recent years certain specialized uses for pyrophyllite have been developed. It is a hydrous aluminum silicate, Al<sub>2</sub>Si<sub>4</sub>O<sub>10</sub>(OH)<sub>2</sub>, whereas talc is a hydrous magnesium silicate. Pyrophyllite sometimes is classed as one of the kaolin minerals. duction and sales figures for pyrophyllite are available for publication separately in 1942 for the first time.

Salient statistics of the talc, pyrophyllite, and ground-soapstone industries in the United States, 1941-42

	19	41	19	42
	Short tons	Value	Short tons	Value
Mined: Total Used by producers	414, 544 370, 444	(2) (2)	403, 801 354, 126	(2) (2)
Sold by producers— Crude <sup>3</sup> Sawed and manufactured Ground	43, 823 4, 186 368, 360	\$393, 839 308, 467 3, 999, 586	33, 837 1, 505 352, 621	\$303, 166 370, 631 4, 080, 279
	416, 369	4, 701, 892	387, 963	4, 754, 076
Imports for consumption: * Crude and unground steatite and French chalk Crut and sawed Ground, washed, or pulyerized	341 71 18, 225	5, 780 10, 611 225, 857	292 (5) 8, 487	5, 849 36 94, 591
하시다 생생이 되었습니다.	18, 637	242, 248	8,779	100, 476
Exports: Talc, steatite, soapstone, and pyrophyllite, crude and ground. Powder—talcum (in packages), face, and compact.	10, 889 (6)	216, 440 1, 229, 280	9, 246 (6)	191, 900 678, 313
u <u>게 하다 중요한테 그리 병원이 대한 다고 되었다.</u>		1, 445, 720		870, 213

<sup>&</sup>lt;sup>1</sup> Bureau of Mines not at liberty to publish pyrophyllite figures separately for earlier years. In 1942: Mined, 53,247 short tons. Sold—crude, 6,440 tons, \$35,790; ground, 47,229 tons, \$379,026; total, 53,669 tons, \$414,816. <sup>2</sup> Data not available.

Thirteen States reported sales of talc, pyrophyllite, ground soapstone, or pinite in 1942—2 more than in 1941. Alabama and New Mexico were new producers. The Eastern States furnished 83 percent of total domestic sales, the same as in 1941.

Descriptions have recently been published of several domestic talc

deposits.

To provide adequate supplies of steatite talc for military use and to prevent its dissipation into uses for which suitable substitutes were available, the War Production Board issued Conservation Order M-239 October 13, 1942, forbidding the use, sale, and delivery of steatite talc except for (1) insulators in communications, radio, radar, and underwater sound instruments; (2) spark plugs for certain war industries; (3) filtering of foods, flavoring extracts, and medicines; and (4) medicines and health supplies, but not including talcum powder or cosmetics. This order was amended February 6, 1943, and certain essential uses formerly forbidden were permitted. These included its

<sup>8</sup> Includes pinite from Nevada.

Exclusive of "manufactures, n. s. p. f., except toilet preparations," as follows: 1941, \$11,701; 1942, \$2,704. Quantities not available.

Less than 1 ton.

<sup>6</sup> Quantity not recorded.

<sup>&</sup>lt;sup>2</sup> McMurray, Lynn, and Bowles, Edgar, The Talc Deposits of Talladega County, Ala.: Geol. Survey Alabama Circ. 16, University of Alabama, 1941, 31 pp.
Bureau of Economic Geology, Soapstone of Northeastern Gillespie County, Tex.: Mineral Resource Survey Circ. 55, University of Texas, Austin, Tex., 1942, 10 pp.
Bureau of Mines, Johnny Gulch Talc Deposit, Madison, Mont.: War Minerals Report 178, 1943, 9 pp.
Page, B. M., and Wright, L. A., Talc in the Ganim Mine, Shasta County, Calif.: Geol. Survey, Strategic Minerals Investigations Preliminary Maps, 1943.

use in electrical and heat insulating products (not including refractories), electric light bulbs, and experimental work. Changing conditions in the talc industry, altering the supply and demand situation, resulted in the issuance on April 29, 1943, by the War Production Board of another amendment to M-239, which removed the existing restrictions on the delivery and use of steatite talc for other than specified uses, established control over production and grading of steatite talc, provided a system of inventory control based upon maximum consumer stocks, and released all frozen stocks of steatite talc purchased before the original issuance of M-239 on October 13, 1942.

Stock-piling of steatite talc was started by Metals Reserve Co.

early in 1943.

SALES

In 1942 producers sold or used 28,406 short tons less of talc, pyrophyllite, and ground soapstone than in 1941, but because of an increase in average value the total value of the sales was \$52,184 greater, reaching a new all-time high record of \$4,754,076. Sales of crude, sawed and manufactured, and ground materials were all lower in 1942 than in the previous year.

Talc, pyrophyllite, and ground soapstone sold by producers in the United States, 1938-42, by classes

	•	Crude		Sawed	and manufa	ctured	
Year	Value at shipping point			Short tons			
	tons	Total	Average	, VI	Total	Average	
1938	13, 498 15, 722 2 17, 724 2 43, 823 2 33, 837	\$72,845 82,188 2118,424 2393,839 2303,166	\$5.40 5.23 26.68 28.99 28.96	1,729 1,871 1,894 4,186 1,505	\$70, 268 77, 915 140, 565 308, 467 370, 631	\$40. 64 41. 64 74. 22 73. 69 246. 27	
		Ground			Total		
	. May de	Value at shipping point		Short	Value at shipping point		
Year	Short	ρο.					
rear	Short tons	Total	Average	tons	Total	Average	

<sup>&</sup>lt;sup>1</sup> Bureau of Mines not at liberty to publish pyrophyllite figures separately for earlier years. In 1942: Crude. 6,440 tons, \$35,790; ground, 47,229 tons, \$379,026; total, 53,669 tons, \$414,816.

<sup>1</sup> Includes pinite from Nevada.

Sales by States.—The tonnages sold or used by producers declined in most of the States for which comparative figures can be shown for 1941 and 1942. Declines were greatest in New York (11 percent), North Carolina (12 percent), and California (13 percent). Georgia was the only State in 1942 to attain a new all-time high record. New York was by far the outstanding producer, and its output was double that of any other State. North Carolina was the only State marketing pyrophyllite. Sales figures for this commodity are available for publication for the first time.

Tale, pyrophyllite, and ground soapstone sold by producers in the United States, 1941-42, by States

State	.19	<b>a</b>	1942	
	Short tons	Value	Short tons	Value
California. Georgia. Maryland Nevada i. New York North Carolina Vermont. Washington Other States 3.	59, 203 28, 511 15, 628 13, 178 153, 560 64, 783 57, 248 6 24, 252	\$811, 793 364, 560 105, 363 126, 433 1, 917, 732 567, 921 663, 468 2, 426 142, 196	51, 649 29, 930 15, 294 12, 339 136, 752 2 56, 909 58, 695 7 26, 388	\$678, 906 464, 166 144, 707 236, 033 1, 886, 635 503, 082 659, 314 2, 864 178, 332
	416, 369	4, 701, 892	2 387, 963	1 4, 754, 076

Includes pyrophyllite from North Carolina as follows: 53,669 tons, valued at \$414,816; Bureau of Mines not at liberty to publish figures separately for earlier years.

1941: Montana, Pennsylvania, and Virginia; 1942: Alabama, Montana, New Mexico, Pennsylvania, and Virginia.

#### MARKETS

Five industries—paint, roofing, ceramics, rubber, and paper—consumed 76 percent of the domestic sales of talc, pyrophyllite, and ground soapstone in 1942, according to reports from producers to the Bureau of Mines. Of these five, the paint and roofing industries alone showed increases. The paint industry consumed over 5,000 tons more than in 1941, taking 32 percent of the total compared with 29 percent in 1941. Roofing was the second-largest consuming industry, rising from fourth to second place and consuming 20 percent more in 1942 than in 1941. The ceramic industry, in second place in 1941, took 39 percent less in 1942 than the previous year or a little less than the roofing industry, thus falling into third place. The rubber industry also declined sharply as a market for these commodities (30 percent), going from third to fourth place. Use in paper declined 20 percent but remained in fifth place.

Talc, pyrophyllite, and ground soapstone sold by producers in the United States, 1941-42, by uses

		. 19	941	1942		
Use		Short tons	Percent of total	Short tons	Percent of total	
Ceramics Rubber Roofing Paper Toilet preparations Insecticides Foundry facings Crayons Other uses reported 2		120, 319 78, 990 58, 114 40, 605 37, 884 21, 119 10, 479 6, 705 3, 186 24, 280 14, 688	29 19 14 10 9 5 2 2 2 1 6 3	125, 518 48, 372 40, 487 48, 870 30, 440 18, 902 15, 810 7, 822 1, 474 27, 631 22, 637	32 13 10 13 8 5 - 4 2 (1) 7	
		<sup>3</sup> 416, 369	100	<sup>2</sup> 387, 963	100	

Less than 0.5 percent.
 1941: Bleaching, insulation, lubricants, refractory, textile, and other minor uses; 1942: Refractory, chemical war service, insulation, plastics, bleaching, textile, lubricants, and other minor uses.
 Includes pinite.

#### PRICES

The average values of sales of all grades of talc, pyrophyllite, and ground soapstone in the past 5 years, as reported to the Bureau of Mines by producers, are given in the table under Sales.

Quotations on ground domestic talc, per ton, f. o. b. works, on June 21, 1943, according to the Oil, Paint and Drug Reporter, were as

follows:

California: \$17.50 to \$43.00.

New York: Fibrous, coarse, off-color, \$13.00. Fine, 325-mesh, 93 to 94 percent, \$13.00 to \$18.00; 98 to 99.5 percent, \$15.25 to \$19.25; 99.85 to 99.95 percent, \$17.00 to \$21.00.

Pennsylvania: \$11 to \$13.50.

Vermont: \$14.00.

Canadian talc, bags, carlots, per ton, \$24.00 to \$30.00.

The quoted prices on pyrophyllite in the same journal were: Standard, 200-mesh, carlots, paper bags, mines, per ton, \$10.00; 325-mesh, same basis, ton, \$13.00; No. 3, 200-mesh, carlots, mines, ton, \$8.00; 325-mesh, same basis, \$11.00.

## DEVELOPMENTS IN THE INDUSTRY

Talc.—Thurnauer and Rodriguez 3 define "steatite" as a group of ceramic materials that contain hydrous magnesium silicate (talc or soapstone) as a predominant constituent in the unfired condition. survey of the literature on the crystal structure of calcined talc and steatite materials is given. The changes in the structure of four typical tale and steatite bodies brought about by varying heat treatment and by the addition of different fluxes were studied. Only two crystal modifications of magnesium metasilicate were observed under the conditions of the investigation. One was the unstable form, protoenstatite, and the other the stable modification, clinoenstatite. Great differences in the rate of crystal growth and extent of polymorphic transformation of one magnesium metasilicate modification into another were observed in the different bodies. Protoenstatite was always found during the early stages of firing or when the crystals remained small, whereas clinoenstatite appeared when the crystals were large. Weakening of the body appeared to be caused by the mechanical cracking of the large crystals of clinoenstatite. Provided the crystals are kept small enough (-7 microns) the body would remain dense, regardless of the number of firings it received.

Relatively small quantities of steatitic talc porcelains were used before the war in radio equipment; their main ingredient was hand-picked talc, largely from a single California source. With the development of a greatly increased war demand, the location of additional sources became imperative. Most talcs are unfit for use in these highly specialized bodies, as they usually contain too much iron and lime as impurities. Some talcs, however, may be beneficiated and brought up to grade—that is, having a content of less than 1 percent each of Fe<sub>2</sub>O<sub>3</sub> and CaO. A talc giving excessive firing shrinkage is also undesirable, and the final test of suitability is whether a fired ceramic

<sup>&</sup>lt;sup>3</sup> Thurnauer, Hans, and Rodriguez, A. R., Notes on the Constitution of Steatite: Jour. Am. Ceram. Soc., vol. 25, No. 15, November 1, 1942, pp. 443-450.

<sup>4</sup> Ralston, O. C., and Stern, A. G., Report of the Nonmetals Division, Fiscal Year 1942; Bureau of Mines Rept. of Investigations 3675, 1942, p. 21.

body containing the talc makes an acceptable insulator. The Bureau of Mines made a Nation-wide search for talcs meeting these specifications. Field engineers inspected the deposits and collected the samples, which were analyzed and evaluated at the Tuscaloosa (Ala.) laboratory. Beneficiating tests were made on all but the most hopeless, and if the results were at all promising large batches were beneficiated and prepared for testing at the Norris (Tenn.) laboratory in regular bodies for electrical and other properties. Some promising talcs were found in California and Alabama. In the East there are large talc deposits in Alabama, North Carolina, Virginia, and New York, which seem unusually good, especially if processed according to modern flotation milling methods. The Bureau of Mines developed methods for treating domestic tales and processed several million radio insulators.

Late in 1942 Gunzenhauser<sup>5</sup> presented the third of a series of articles on steatite and special ceramic materials used for electrical insulating parts; he discussed the physical properties of such materials

in this latest paper.

The use of a steatite body by the Star Porcelain Co., Trenton, N. J., in the manufacture of porcelain welding ferrules is described

in a recent article.6

Hendricks 7 discussed the lattice structure of talc and pyrophyllite. Rigterink, Grisdale, and Morgan<sup>8</sup> prepared a number of steatite bodies under carefully controlled conditions and measured their dielectric losses and direct-current resistances at elevated temperatures. It was found that variations of the ratio of talc to kaolin within certain limits had little effect on the dielectric properties. These properties, however, were changed to a considerable extent by varying the amounts, proportions, and kinds of alkaline-earth oxides added as The data indicate also that the conditions in a ceramic body favorable to a high specific resistance are not necessarily those favorable to a low dielectric loss.

The results of tests on the thermal-expansion characteristics of steatite by Rigby and Green, originally published in 1941, were re-

printed in 1942.

Tremolitic talc dust has been classed as a silicate dust capable of causing a disabling pneumoconiosis.10 Other papers relating to talc as an occupational hazard are those by Schultz and Williams 11 and Snyder.12

Pyrophyllite.—The pyrophyllite open-pit mine and mill of the Carolina Pyrophyllite Co., Randolph County, N. C., are described

Gunzenhauser, A., Physical Properties of High Frequency Electrical Ceramic Insulating Parts: Ceram. Ind., vol. 39, No. 5, November 1942, pp. 68, 70, 72.
Ceramic Industry, Porcelain Welding Ferrules Made by Regular Steatite Production Methods: Vol. 39, No. 1, July 1942, pp. 42-43.
Hendricks, S. B., Lattice Structure of Clay Minerals and Some Properties of Clay: Jour. Geol., vol. 50, 1042 pp. 758-900

<sup>&</sup>lt;sup>7</sup> Hendricks, S. B., Lattice Structure of Cray Minerals and Some Properties of Cas., 1942, pp. 276-290.

<sup>8</sup> Rigterink, M. D., Grisdale, R. O., and Morgan, S. O., Relation Between Chemical Composition and Dielectric Properties of Ceramic Materials with Low Dielectric Losses: Jour. Am. Ceram. Soc., vol. 25, No. 15, November 1, 1942, pp. 439-448.

<sup>9</sup> Rigby, G. R., and Green, A. T., Thermal-Expansion Characteristics of Some Calcareous and Magnesium Minerals: Bull. British Refrac. Research Assoc., No. 58, 1941; reprinted in Trans. British Ceram. Soc., vol. 41, No. 5, 1942, pp. 123-143. Ceram. Abs. (Am. Ceram. Soc.), vol. 21, No. 11, November 15, 1942, p. 249.

<sup>10</sup> Porro, F. W., Patton, J. R., and Hobbs, A. A., Jr., Pneumoconiosis in the Tale Industry: Am. Jour. Roentgenol. and Radium Therapy, vol. 47, April 1942, pp. 507-524.

Siegel, W., Smith, A. R., and Greenburg, Leonard, Dust Hazards in Tremolitic Tale Mining, Including Roentgenological Findings in Tale Workers: Am. Jour. Roentgenol. and Radium Therapy, vol. 49, January 1943, pp. 11-29.

Hoentgenooigal rindings in Tale workers. Am. 3001. Rochigeno. and Radical Palegy, vol. 2, 301 uary 1943, pp. 11-29.

11 Schultz, R. Z., and Williams, C. R., Commercial Tale. Animal and Mineralogic Studies: Jour. Ind. Hyg. and Toxicol., vol. 24, April 1942, pp. 75-79.

12 Snyder, C. A., Why Industrial Dust Control is Necessary: Occupational Hazards, vol. 5, No. 2, 1942, p. 9; Canadian Machinery, vol. 53, No. 11, 1942, p. 94.

in a recent article.<sup>13</sup> Air drills are used in mining. The broken pyrophyllite, hand-loaded on 6-ton trucks, is dumped into open storage or bins at the mill. It is crushed in a 12- by 24-inch Reliance jaw crusher set to 1 inch; the crushed material is then elevated to two surge bins, one for each of the two mill units. Each of these units is equipped with a Hardinge conical mill, 8 feet by 36 inches in one and 8 feet by 80 inches in the other, each being followed by a 14-foot Gayco separator. Oversize from each separator is sent back to the corresponding mill. The finished material is delivered to a bin, from which it is shipped in bulk or bagged. Salisbury (N. C.) granite blocks are used to line the Hardinge mills; this granite is also used as the grinding medium, replacing Belgian flint pebbles. Ground products shipped range from 80- to 325-mesh. Rock crushed to one-half inch and three-fourths inch has also been shipped.

Hendricks' discussion of the lattice structure of pyrophyllite has

already been mentioned.14

## FOREIGN TRADE 15

Imports.—Total tale, steatite or soapstone, and French chalk imports in 1942 dropped 53 percent in quantity and 59 percent in value




FIGURE 2.—Talc, steatite or soapstone, and French chalk imported for consumption in the United States, 1940-42, by leading countries.

from 1941. Nearly all of the imports consisted of materials "ground, washed, powdered, or pulverized, except toilet preparations," only a few hundred tons being of "crude and unground" and "cut and sawed" materials. India furnished 286 tons of crude block steatite, as well as considerable ground steatite. Imports in 1942 came principally from Canada and British India (see fig. 2); only minor

<sup>&</sup>lt;sup>12</sup> Engineering and Mining Journal, United Feldspar's Pyrophyllite Enterprise: Vol. 144, No. 4, April 1943, pp. 69-71

<sup>1943,</sup> pp. 69-71.

14 Hendricks, S. B., Work cited in footnote 7.

15 Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

quantities came from Japan and United Kingdom. Imports incorrectly reported as from Kwantung (Japanese-leased territory) in the import tables in the Talc chapter, Minerals Yearbook 1941 (p. 1397),

actually came from British India.

Steatite talc imports were placed under import control November 23, 1942 (General Imports Order M-63, December 27, 1941, Federal Register, vol. 6, No. 252, December 30, 1941, pp. 6796-6797, as amended November 20, 1942, Federal Register, vol. 7, No. 230, November 24, 1942, pp. 9702-9703).

Talc, steatite or soapstone, and French chalk imported for consumption in the United States, 1938-42, by classes

Year		e and ound	powder verize	l, washed, ed, or pul- d, except eparations	sav	and red	Т	otal		
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
1938 1939 1940 1941 1942	337 133 93 341 292	\$5, 956 2, 392 1, 479 5, 780 5, 849	21, 568 25, 943 28, 145 18, 225 8, 487	\$351, 541 408, 178 465, 049 225, 857 94, 591	129 94 125 71 (3)	\$7,866 14,651 20,739 10,611	22, 034 26, 170 28, 363 18, 637 8, 779	\$365, 363 425, 221 487, 267 242, 248 100, 476	93 98 (1) (1) (1)	\$25, 835 27, 398 21, 568 11, 701 2, 704

<sup>1</sup> Quantity not recorded.
2 Less than 1 ton.

Talk, steatite or soapstone, and French chalk imported for consumption in the United States, 1941-42, by classes and by countries

Country	Crude and unground		Ground, washed, powdered, or pulverized, ex- cept toilet preparations		Cut and sawed		Total		Manu- fac- tures, n. s. p. f., except toilet
	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	prepa- rations (value)
1941 Canada. China France. Hong Kong	2 66	\$14 562	7, 018 3, 810 250	\$73, 941 39, 990 6, 587			7, 020 3, 876 250	\$73, 955 40, 552 6, 587	\$11,074
India, British Italy Japan Kwantung Union of South Africa United Kingdom	248 25	4, 397 	5, 278 20 1, 507 342	75, 532 519 25, 515 3, 773	71	\$10,611	5, 526 20 1, 578 342 25	79, 929 519 36, 126 3, 773 807	539
• W - T - 1	341	5,780	18, 225	225, 857	71	10, 611	18, 637	242, 248	11,701
1942 Canada China	6	96	6, 296	62, 126			6, 302	62, 222	7 510
Hong Kong	286	5,753	1,963 9 219	28, 863 259 3, 343	(1)	36	2, 249 9 219	34, 616 295 3, 343	2, 186 1
	292	5, 849	8, 487	94, 591	(1)	36	8, 779	100, 476	2, 704

Less than 1 ton.
 United Kingdom of Great Britain and Northern Ireland.

Exports.—The quantity of "talc, steatite, soapstone, and pyrophyllite, crude and ground" exported from the United States reached an all-time record of 10,889 short tons in 1941 but was 1,643 tons less in 1942. The value of "powders—talcum (in packages), face, and compact," exported in 1941 was higher than in any year since 1931, but the value of the exports in 1942 was 45 percent less than in 1941.

Talcum and other powders exported from the United States, 1938-42

	Short	Va Va	lue
Year Description	tons	Total	Average
1938	_1 (*)	\$124, 194 978, 100 162, 426 1, 115, 176 167, 992 945, 530 216, 440 1, 229, 280 191, 900 678, 313	\$17, 45 17, 95 17, 87 19, 88 20, 75

<sup>1</sup> Quantity not recorded.

## WORLD PRODUCTION

Production figures for talc, pyrophyllite, and soapstone in 1942 are lacking for most countries.

World production of tale, pyrophyllite, and soapstone, 1937-42, by countries, in metric tons 1

[Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
Argentina. Australia: New South Wales South Australia	991	80 597 973	303 (³) 1,115	1, 168 (3) 1, 349 (3)	1, 975 (2) 2, 972 (3)	(2) (3) (2) (2) 14, 183
Tasmania Canada <sup>3</sup> China (Manchuria) (exports) Egypt Finland France Company	111,140	9,846 81,215 1,251 (1)	11, 924 93, 772 833 (1)	13,758 4 72,495 2,212 (3) (2)	16, 484 (3) 5, 229 (2) (2)	14, 183 (2) (3) (2) (2)
Germany: Austria (exports) Bavaria: Greece: India, British Indochina Italy	1,838 13,249 428	5, <b>62</b> 5 6, 805 1, 293 18, 888	(3) (3) 1,003 22,616 400 (2)	(3) (2) (3) (3) (3) (3)	999999	99999
Morooco, French (exports)	841 (2) 24,701 1,976	1,702 1,605 23,703 2,256 8,438 6,797	(3) (2) (3) (3) (3) (4) (5) 7, 195	(3) (2) (3) (2) (3) (4) (4)	(2)	000000
Sweden Tanganyika Territory Union of South Africa: Transvaal United States • Uniguay (exports)	376 208,650 437	38 1, 554 193, 025 952	230, 402 1, 111	1,757 255,258 1,699	4 1, 379 377, 722 1, 867	(3) 4 1, 28 351, 95 7 2, 19

<sup>&</sup>lt;sup>1</sup> In addition to countries listed tale or pyrophyllite is reported produced in Brazil, Bulgaria, U. S. S. R., and Western Australia but data on production are not available.

and Western Australia but data on production are not available.

3 Data not available.

5 Excludes scapstone, which is reported only by value and was as follows: 1937, \$40,513; 1938, \$35,038; 1939, \$41,471; 1940, \$74,905; 1941, \$155,925; 1942, \$121,766. Scapstone is sold in the form of both blocks and powder.

4 January to September, inclusive.

5 Includes steatite, as follows—1937: 500 tons; 1938; 3,480 tons; 1940: 17,191 tons.

6 Talc, pyrophyllite, and ground scapstone sold by producers; includes also pinite in 1940, 1941, and 1942.

7 January to June, inclusive.

Canadian talc and soapstone developments in 1941 have been described as follows:16

Active production of ground tale in Canada was begun in 1906 from deposits Active production of ground tale in Canada was begun in 1900 from deposits in the Madoc area, Ontario, and these deposits have since been the main source of supply. Canada Talc, Limited, is the chief producer in the area, having taken over the holdings of G. H. Gillespie Company, the pioneer operator, in 1937. There have been various other small operations in the area. In 1941, Trent Mining Syndicate began to develop a property adjoining that of Canada Talc, Limited, where surface showings indicate an easterly extension of the same vein system, and at the end of the year was proceeding with the erection of a small mill. R. W. Bonter and associates of Trenton ground a small tonnage of slightly off-color tale in the mill of Canadan Slate Products a mile and a half north of Madoc; the in the mill of Canadian Slate Products, a mile and a half north of Madoc; the crude was brought in by truck from a deposit operated by W. C. Spry near Ompah, Frontenac County, 65 miles distant. The talc from Ompah is finely schistose, cream-colored, and distinct in character from the white foliated tale of the Madoc district.

In British Columbia, the deposits near McGillivray, on the Pacific Great Eastern Railway, and at Kapoor, near Victoria, have been idle since 1935. crude was shipped to a grinding plant at Vancouver, for local roofing use.

Quebec has been supplying soapstone in small quantities since 1922, and the industry has been supplying soapstone in smail quantities since 1922, and the industry has been supplying mainly blocks and bricks for alkali recovery furnaces of domestic kraft mills. Some cut furnace stone has been exported. In recent years the sawing of crayons has been undertaken. Broughton Soapstone and Quarry Company, the principal operator, has developed a large quarry near Leeds Station on the Quebec Central Railway, in Broughton Township. This company produces cut furnace stone and grayons and has confidence mill in this company produces cut furnace stone and crayons and has a grinding mill in which quarry produces cut rurnace stone and crayons and has a grinding min in which quarry and sawing waste, as well as a more highly talcose rock occurring in a band cutting its main soapstone body, are pulverized. The company took over the Louis Cyrholdings at St. Pierre de Broughton in 1940. Other operators in the same area are Charles Fortin, of Robertson, and L. C. Pharo, of Thetford Mines. L. C. Pharo installed a small grinding unit on his property in Thetford township in 1938. Some of the dust from these operations is sold to domestic roofing firms, and a considerable tonnage of quarry and sawing waste is shipped to the grinding plant of Pulverized Products, Limited, 4820 Fourth Avenue, Rosemount, Montreal, the only other operator in Quebec, has a mine and mill near Highwater in Potton township, Brown County, clear to the Vernand Line. township, Brome County, close to the Vermont line.

Extensive studies on steatite deposits in Canada are reported, and a steatite industry is said to have been established.17 In Quebec the output of talc and soapstone in 1942 increased over 1941.18

In the U.S.S.R. the large agalmatolite deposits in the Ak-Tash region of Central Asia and tests of this material for porcelain and faience production were described recently by Vikhireva.19

Steatite was produced in Western Australia in 1942.20

<sup>16</sup> Canada, Department of Trade and Commerce, The Talc and Soapstone Industry, 1941: Dominion Bureau of Statistics, Mining, Metallurgical and Chemical Branch, Ottawa, Canada, 1942. (Data abstracted from report on Talc and Soapstone by the Bureau of Mines, Ottawa, Olanda, 1942. (Data abstracted from report on Talc and Soapstone by the Bureau of Mines, Ottawa, Olanda, 1942. (Data abstracted from report on Talc and Soapstone by the Bureau of Mines, Ottawa, Olanda, 1942. (Data abstracted from Parketin, C. C., Ceramic Lines Widen Rapidly in War Effort: Clay Prod. News, vol. 16, No. 1, 1943, p. 3.

18 DeMille, J. B., Mining in Quebec in 1942: Canadian Min. Jour., vol. 64, No. 2, 1943, pp. 84–88.

19 Vikhireva, L. A., Use of the Raw Materials of Middle Asia in Porcelain and Faience Production: Keram. Sbornik, No. 13, 1941, pp. 29–37; Ceram. Abs. (Am. Ceram. Soc.), vol. 21, No. 3, March 1, 1942, p. 69.

20 Chemical Engineering and Mining Review, vol. 35, No. 409, October 10, 1942, p. 13.

# FLUORSPAR AND CRYOLITE

By H. W. Davis<sup>1</sup>

#### SUMMARY OUTLINE

the control of the co	Page	the classical states of the state of	Page
Fluorspar	1391	Fluorspar—Continued.	
Summary	1391	Technologic developments	1399
Salient statistics	1392	Fluorspar industry in 1942, by States	1399
Production and shipments	1393	Foreign trade	1407
Shipments, by uses	1395	Imports	1407
Uses	1395	Exports	1408
Specifications	1396	Tariff reduction	1408
Consumption and consumers' stocks	1397	World production	1408
Prices	1398	Cryolite	1410
Stocks at mines or shipping points	1399	Imports	1411

## **FLUORSPAR**

#### SUMMARY

The period of intense activity in fluorspar mining, which began in 1940, continued unabated throughout 1942. Despite some strikes, manpower shortage, and other handicaps, production and shipments (337,000 and 360,316 short tons, respectively) in 1942 were 8 and 12 percent greater than in 1941, the previous record year, and shipments were 37 percent more than in 1918 during World War I. Attaining first place in 1942, Illinois shipments (161,949 tons) exceeded by 3.4 percent the previous high (156,676 tons) reached in 1917. New Mexico and Utah also established new records in 1942. Shipments from Kentucky in 1942 were 6 percent under the all-time record made in 1941. Shipments by river or river-rail (79,049 tons) also made a new record in 1942. However, imports, amounting to 2,151 tons, declined 71 percent from 1941 and were smaller than in any year since records were first kept (1910). Exports, which are usually small, decreased 26 percent but for the second time exceeded imports.

During 1942 much prospecting and development work were done; probably more shafts were sunk and more mills were constructed than in any one previous year. However, because of a shortage of labor and the need to use most of the available manpower to mine ore, many producers could not keep their development as far ahead

of mining as was desirable.

Notwithstanding the record production of fluorspar in 1942, the output of metallurgical grade did not keep pace with consumption; as a consequence, inventories at consuming plants declined substantially. Fortunately, the monthly survey of fluorspar, inaugurated by the Bureau of Mines in January 1942, reflected the lag in production in the early part of 1942, and the War Production Board was able to take corrective action much sooner than would have been possible had monthly data not been available. Among other things this action included an extensive examination of deposits in the Illinois-Kentucky district and in the West by the Geological Survey, a drilling and development program in these areas by the Bureau

<sup>&</sup>lt;sup>1</sup> Figures on imports (unless otherwise indicated) compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce; those on exports of fluorspar supplied by the producers.

of Mines, an increase in maximum price, and a change in specifica-tions. Based upon the field work of the Bureau of Mines and upon data made available from other sources, a number of war minerals reports 2 on fluorspar have been prepared for the confidential use of Federal war agencies.

Salient statistics of the fluorspar industry in the United States, 1941-42

하는 것으로 하는 것으로 보는 것으로 기록되는 것들이 되었다. 1980년	19	41	19	12
하는 것이 되었다. 그 사람이 그 사람이 사람들은 아니다. 그들은 사람들이 되었다. 사용한 사람들이 가장 보고 있는 것이 되었다. 그 사용이 가장 사용한 것이 되었다. 사용한 사람들은 사용한 사용한 사용한 사용한 사용한 사용한 사용한 기업을 받았다.	Short tons	Value	Short tons	Value
Shipments from domestic mines— To consumers in United States: Metallurgical Ceramic Chemical To consumers in foreign countries	222, 832 32, 979 52, 674 12, 184	\$4, 239, 436 847, 941 1, 359, 623 277, 782	240, 088 23, 126 88, 086 9, 016	\$5, 473, 82 640, 51 2, 540, 86 242, 54
그리겠다 아이들이 맛있다고 있었다. 교리 2005년	320, 669	6, 724, 782	360, 316	8, 897, 74
Stocks at mines or shipping points Dec. 31: Finished Crude	31, 997 40, 200	(1)	19, 429 32, 181	(3)
	72, 197	(1)	51, 610	(1)
Imports for consumption— Containing more than 97 percent CaF <sub>2</sub> Containing not more than 97 percent CaF <sub>3</sub>	1, 516 6, 008	29, 850 50, 285	1, 882 269	31, 951 3, 578
는 상황원 (1995) (1995) 1일 1일 1일 1일 1일 1일 1일 1일 1일 1일 1일 1일 1일	7,524	80, 135	2, 151	35, 52
Consumption (by industries): Metallurgical Ceramic Chemical	219, 100 28, 500 56, 000	e) e) e) e)	257, 200 22, 000 81, 600	6)
[첫[孝글, 121] : 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1 - 1	303, 600	(1)	360, 800	(1)
Stocks at consumers' plants Dec. 31:  Metallurgical Ceramic Chamical	<sup>2</sup> 90, 800 <sup>2</sup> 7, 900 10, 200	(1) (1) (1)	68, 500 8, 500 19, 000	(1)
	<sup>2</sup> 108, 900	(1)	96,000	(1)

<sup>1</sup> Figures not available.

Despite the fact that demand for metallurgical-grade fluorspar was supplied with some difficulty, no prohibitions or limitations were placed on its use, but the War Production Board requested steel manufacturers to employ fluorspar as sparingly as possible. Although supplies of metallurgical-grade fluorspar were not allocated during 1942, it was necessary to divert shipments to certain consumers who had inadequate supplies. However, beginning January 1943 shipments of both metallurgical and ceramic grades will be controlled by the War Production Board, which will forbid any supplier to ship fluorspar to consumers having an inventory greater than a "practicable working minimum."

Although consumption of acid-grade fluorspar gained remarkably

<sup>2</sup> Revised figures.

<sup>&</sup>lt;sup>2</sup> Mineral Ridge Fluorspar Property, Livingston County, Ky.: Bureau of Mines War Minerals Rept. 18, December 1942, 7 pp.
United States Fluorspar Mine, Sierra County, N. Mex.: Bureau of Mines War Minerals Rept. 21, Decem-

ber 1942, 4 pp.
Fluorspar and Zinc Properties on the Babb and Commodore Faults, Crittenden County, Ky.: Bureau of Mines War Minerals Rept. 23, December 1942, 8 pp.
Spar Mine, Catron County, N. Mex.: Bureau of Mines War Minerals Rept. 24, November 1942, 7 pp.
Illinois-Kentucky Fluorspar District: Bureau of Mines War Minerals Rept. 35, January 1943, 32 pp.
Clum Mine, Grant County, N. Mex.: Bureau of Mines War Minerals Rept. 104, March 1943, 8 pp.
Mirabal Fluorspar Mine, Valencia County, N. Mex.: Bureau of Mines War Minerals Rept. 214, May 1943, 6 pp.

in 1942, production increased still more and in consequence inventories were larger at the end than at the beginning of 1942. Likewise, production of ceramic-grade fluorspar was more than adequate for

consumption which, however, declined in 1942.

Recognizing the importance of fluorspar in the military program, representatives of the Army Air Forces spent considerable time studying the fluorspar plants in southern Illinois; as a result, the Forces took over the responsibility of protecting the plants at Rosiclare against sabotage and other malicious damage. The properties have been fenced, and each plant has a regular force of guards.

At Rosiclare, Ill., a Government housing project involving an expenditure of approximately \$500,000 was started to provide housing

facilities for 150 families.

Sales of fluorspar to consumers in the United States totaled 353,469 short tons in 1942 (351,300 tons from domestic mines and 2,169 tons from foreign sources) compared with 316,074 tons in 1941 (308,485 tons from domestic mines and 7,589 tons from foreign sources). sales to steel plants in the United States advanced to 225,502 tons in 1942 from 220,222 tons in 1941, and sales to domestic manufacturers of hydrofluoric acid (essential in the manufacture of artificial cryolite and aluminum fluoride—aluminum raw materials) increased to 89,983 tons from 54,092 tons, but sales to domestic makers of glass and enamel declined to 22,813 tons from 32,051 tons.

The greatly accelerated demand for fluorspar in 1942 was accompanied by an advance in prices. The average composite selling price (\$24.66) of all grades (both domestic and foreign) delivered to consumers in the United States was \$3.68 more than in 1941 (\$20.98). The average selling price f. o. b. Illinois-Kentucky mines of fluorspar shipped to domestic steel plants was \$23.82 a short ton (\$19.62 in 1941), of that shipped to domestic manufacturers of hydrofluoric acid \$28.86 (\$26.78 in 1941), and of that shipped to domestic makers

of glass and enamel \$29.44 (\$27.39 in 1941).

Effective November 23, 1942, the Office of Price Administration established new base ceiling prices for metallurgical-grade fluorspar ranging from \$25 to \$28 a short ton according to calcium fluoride and These prices compared with previous prices of \$23 to silica content. \$25 a ton for standard metallurgical grade in the Illinois-Kentucky The new prices are subject to freight adjustments. the same time, a price of \$32 a short ton, subject to freight adjustments, was established for acid-grade fluorspar (except in the Illinois-Kentucky district) containing a minimum of 97½ percent calcium fluoride and a maximum of 1½ percent silica.

In the trade agreement between the United States and Mexico, the duty on fluorspar containing not more than 97 percent calcium

fluoride was lowered to \$5.62½ a short ton from \$7.50.

The total quantity of fluorspar shipped in and imported into the United States from about 1870 through 1942 was approximately 6,270,000 short tons, comprising 5,209,000 tons from domestic mines and 1,061,000 tons from foreign sources.

## PRODUCTION AND SHIPMENTS

Production of fluorspar (expressed in terms of finished product) totaled 337,000 short tons in 1942 compared with 313,000 tons in 1941. Of the output in 1942, 10 mines producing over 10,000 tons each supplied 156,000 tons or 46 percent, 12 mines producing 5,000 to 10,000 tons each supplied 83,000 tons or 25 percent, and 26 mines producing 1,000 to 5,000 tons each supplied 65,000 tons or 19 percent; thus, 48 mines produced 304,000 tons or 90 percent of the total. The remainder (33,000 tons or 10 percent) was produced in quantities ranging from a few tons to 1,000 tons from an undetermined number of small mines and prospects and reclaimed from waste dumps and old workings of abandoned mines.

Fluorspar shipments from domestic mines in 1942 aggregated 360,316 short tons valued at \$8,897,749, increases of 12 percent in quantity and 32 percent in total value over 1941, and were the largest on record. Of the 1942 total, 79,049 tons (an all-time high) was shipped by river or river-rail for delivery to consumers in Illinois, Indiana, Kentucky,

Ohio, Pennsylvania, and West Virginia.

Illinois (45 percent) and Kentucky (37 percent) supplied 82 percent of the fluorspar shipped in 1942 compared with 86 percent in 1941. Shipments from the Illinois-Kentucky district in 1942 gained only 7 percent over 1941 compared with an increase of 44 percent in the West.

In 1942 mines operated by consumers shipped about 92,000 short tons of fluorspar for use in their own plants compared with 59,644 tons in 1941.

The average value of all grades of domestic fluorspar shipped in 1942 was \$24.69 a short ton (\$3.72 more than the 1941 average).

The following table shows shipments of fluorspar, by States, 1941 and 1942. (For historic table, see Minerals Yearbook, 1941, p. 1401.)

Fluorspar shipped from mines in the United States, 1941-42, by States

하이다. 등 되는 그리큐를 보는 것이라고 1889년 등 다시 아이들은 그 같은 말을 했다.		1941		1942				
State	G1 44	Value			Va	Value		
	Short tons	Total	Average	Short tons	Total	Average		
Colorado Illinois Kentucky Arizona	15, 566 133, 333 142, 862	\$225, 069 3, 047, 247 2, 957, 982	\$14.46 22.85 20.71	31, 743 161, 949 134, 133	\$640, 938 4, 306, 750 3, 266, 257	\$20.19 26.59 24.35		
New Mexico	19, 089	355, 951	18.65	23, 291	<sub>*</sub> 530, 025	22. 76		
Nevada	8, 967 748 104	138, 533	14.11	8,020 1,018 48 114	153, 779	16.72		
	320, 669	6, 724, 782	20. 97	360, 316	8, 897, 749	24.69		

Ferrous and nonferrous plants are the chief purchasers of fluorspar, taking 66 percent of the total shipped from domestic mines in 1942. Of the fluorspar shipped to these plants in 1942, 97.9 percent was metallurgical grade, 0.5 percent ceramic grade, and 1.6 percent acid grade. Chemical plants, which use acid-grade fluorspar, and glass and enamel makers, which use fluorspar varying widely in calcium fluoride and silica content, took 25 and 6 percent, respectively, of the domestic shipments in 1942.

The next table shows shipments of fluorspar, by grades and indus-

tries, in 1942.

Fluorspar shipped from mines in the United States in 1942, by grades and industries

Grade and industry	<b>.</b>	Value		
	Short tons	Total	Average	
Metallurgical: Ferrous and nonferrous Cement Miscellaneous Exported	233, 658 264 80 3, 330	\$5, 275, 924 5, 871 1, 735 88, 452	\$22.58 22.24 21.69 26.56	
	237, 332	5, 371, 982	22.63	
Ceramic: Glass and enamel Ferrous and nonferrous Cement Miscellaneous Exported	1 22, 813 1, 210 49 1, 307 787	633, 086 32, 524 1, 558 45, 939 27, 993	27. 75 26. 88 31. 80 35. 15 35. 57	
그 젊은 밥 되는 말이 얼마나 아니다 하는데 그래요	1 26, 166	741, 100	28. 32	
Acid: Chemical Ferrous and nonferrous Exported	88, 086 3, 833 4, 899	2, 540, 869 117, 698 126, 100	28. 85 30. 71 25. 74	
이 [취임 : 14] - ' 전시 : 스탈인 : (1) - (1)	96, 818	2, 784, 667	28.76	
Total: Ferrous and nonferrous Glass and enamel Chemical Cement Miscellaneous Exported	238, 701 22, 813 88, 086 313 1, 387 9, 016	5, 426, 146 633, 086 2, 540, 869 7, 429 47, 674 242, 545	22. 73 27. 75 28. 85 23. 73 34. 37 26. 90	
시 및 시 기계, 경기, 경기 등 기계 등 기계 등 기계 등 기계 등 기계 등 기계 등 기계 등	360, 316	8, 897, 749	24. 69	

<sup>1</sup> Of this quantity 2,985 tons were unground, including 2,602 tons of a purity equivalent to metallurgical grade.

SHIPMENTS, BY USES

The steel industry is the predominant purchaser of fluorspar, as is evident from the following table; it also consumes considerable hydrofluoric acid and sodium fluoride, in which fluorspar is the basic material.

Fluorspar shipped from mines in the United States, 1941-42, by uses

	1941				1942			
Use	Quantity		Value		Quantity		Value	
	Percent of total	Short tons	Total	Average	Percent of total	Short tons	Total	Average
Steel Foundry Glass and enamel Hydrofluoric acid Miscellaneous	66. 77 . 85 9. 99 16. 43 2. 16	214, 120 2, 724 32, 051 52, 674 6, 916	\$4,048,454 53,044 839,547 1,359,623 146,332	\$18. 91 19. 47 26. 19 25. 81 21. 16	62. 51 . 95 6. 33 24. 45 3. 26	225, 233 3, 408 22, 813 88, 083 11, 763	\$5, 085, 037 65, 073 633, 086 2, 540, 766 331, 242	\$22, 58 19, 09 27, 75 28, 85 28, 16
Exported	96. 20 3. 80	308, 485 12, 184	6, 447, 000 277, 782	20. 90 22. 80	97. 50 2. 50	351, 300 9, 016	8, 655, 204 242, 545	24. 64 26. 90
	100.00	320, 669	6, 724, 782	20.97	100.00	360, 316	8, 897, 749	24.69

## USES

As figure 1 shows graphically, the steel industry is the chief consumer of fluorspar in the United States. Fluorspar is used as a flux in basic open-hearth and basic electric steel furnaces; a comparatively small amount is used in Bessemer-steel furnaces. The second-largest

use is in the manufacture of hydrofluoric acid, which is employed to make artificial cryolite and aluminum fluoride (aluminum raw materials) and refrigerating mediums; hydrofluoric acid is also used in the electrolytic refining of metals, the pickling of metals, chromium plating, the processing of high-octane gasoline and synthetic rubber, and the etching of glassware, as well as for other purposes. The glass industry, which uses fluorspar as an opacifier and as a flux, ranks third in importance. The enamel industry uses fluorspar as an ingre-




FIGURE 1.—Average annual fluorspar sales (domestic and foreign) to consumers in the United States, 1937-41, compared with 1942, by consuming industries and by sources.

dient in frit; it formerly ranked fourth but dropped to sixth place in 1942. Comparatively small quantities of fluorspar are used in a number of miscellaneous operations, such as production of the finer grades of iron castings, chilled-iron rolls, brass and bronze ingots, nickel and Monel metal, aluminum, magnesium, tin, cement, ferro-alloys, carbon electrodes, rock wool, and calcium carbide and cyanamid; in smelting refractory ores of gold, silver, and copper; as a paint pigment; as a binder for abrasives; in a formula for coating welding rods; as a boiler-cleaning compound; as a flux to deslag high-pressure steam generators; for stripping anodizing racks; as an ingredient in various types of fluxing compounds; and in a special cement used to produce a coating for artificially colored roofing granules for camouflage purposes.

#### SPECIFICATIONS

The chief commercial grades of fluorspar are metallurgical, ceramic, and acid. The standard chemical specification for metallurgical

grade is a minimum of 85 percent calcium fluoride and a maximum of 5 percent silica and 0.3 percent sulfur. However, under pressure of increasing demand and as a result of a change in the ceiling-price structure, metallurgical-grade fluorspar containing less calcium fluoride and more silica is being accepted by many consumers. The standard chemical specification for acid-grade fluorspar is a minimum of 98 percent calcium fluoride and a maximum of 1 percent each of silica and calcium carbonate, but a product containing 97½ percent calcium fluoride and 1½ percent silica is now being accepted by consumers. The specifications for ceramic-grade fluorspar vary widely, but the standard specification is a minimum of 95 percent calcium fluoride and a maximum of 2½ percent silica.

# CONSUMPTION AND CONSUMERS' STOCKS

The following tables give data on consumption and consumers' stocks of fluorspar.

Fluorspar (domestic and foreign) consumed and in stock in the United States, 1941-42, by industries, in short tons

	19	41		1942	
Industry	Consump- tion	Stocks at consumers' plants Dec. 31	Consump- tion	Stocks at consumers' plants Dec. 31	In transit to consumers' plants Dec. 31
Basic open-hearth steel Electric-furnace steel Bessemer steel Iron foundry Ferro-alloys Hydrofluoric acid Primary aluminum Primary magnesium Glass Enamel Cement Miscellaneous	191, 300 18, 300 2, 600 2, 500 56, 000 800 300 27, 600 900 2, 500	1 86, 800 1 1, 300 1, 000 10, 200 400 100 1 5, 300 1 2, 300 1 1, 200	217, 100 25, 300 200 3, 600 4, 200 81, 600 2, 000 700 18, 500 3, 100 400 4, 100	63, 400 1, 100 1, 000 19, 000 1, 100 400 7, 200 1, 100 200 1, 500	4, 084 57 58 49 59 59 41 122
	303, 600	1 108, 900	360, 800	96, 000	5, 60

<sup>+</sup> Revised figures.

Consumption and stocks of fluorspar (domestic and foreign) at basic open-hearth steel plants, 1938-42

	1938	1939	1940	1941	1942
Production of basic open-hearth steel ingots and castingslong tons.	25, 868, 000	43, 368, 000	55, 038, 000	¹ 66,056, 000	67, 821, 000
Consumption of fluorspar in basic open-hearth steel production short tons.	73, 600	116, 200	143, 800	191, 300	217, 100
Consumption of fluorspar per ton of steel made pounds_	5.7	5.4	5. 2	5.8	6.4
Stocks of fluorspar on hand at steel plants at end of year	55, 000	69, 900	79, 800	84, 200	60, 400

<sup>1</sup> Revised figures.

The quantity of fluorspar used per long ton of basic open-hearth steel varies with each plant, each operator, each furnace, and each heat but probably ranges from less than 1 to 80 pounds. The average for all plants is generally 5 to 8 pounds—a relatively small proportion of the furnace charge. From 1921 (the first year for which these data were collected) to 1940 the average consumption of fluorspar\_per

long ton of steel made declined almost steadily from 8.2 to 5.2 pounds. However, it increased to 5.8 pounds in 1941 and further to 6.4 pounds in 1942—the highest since 1935. The gain in 1941 and 1942 was due partly to the manufacture of proportionately more armor steel; a poorer quality of scrap, higher charges of lime, and rushing of heats. Although electric-furnace steel plants are small users of fluorspar compared with basic open-hearth steel plants, the average consumption (13.5 pounds in 1942) is substantially greater.

#### PRICES

On January 20, 1942, the Office of Price Administration requested producers of fluorspar "not to publish or quote prices on, nor sell your fluorspar at prices above your prices in effect on January 2, 1942." On January 2 the general price range for standard fluxing gravel fluorspar in the Illinois-Kentucky district was \$23 to \$25 a short ton f. o. b. mines. Inasmuch as production of fluxing gravel fluorspar did not pace consumption, the Office of Price Administration deemed a price increase to be essential to stimulate production and to encourage new producers to enter the fluorspar field. Consequently, new base ceiling prices for metallurgical-grade fluorspar, which became effective November 23 and ranged from \$25 to \$28 a ton, according to calcium fluoride and silica content, were established in Maximum Price Regulation 126 (Fluorspar), issued November 17, 1942. At the same time, dollar-and-cents ceiling prices were established for acid-grade fluorspar, except in the Illinois-Kentucky field. The following excerpts are quoted from Maximum Price Regulation 126.

(a) Metallurgical grade. (1) The maximum price f.o.b. a consumer's plant on any shipment shall be the price for the effective CaF<sub>2</sub> content as listed in the following table, plus either (i) railroad freight on such shipment from the producer's shipping point to the consumer's plant, or (ii) railroad freight on such a shipment from Rosiclare, Ill., to the consumer's plant, whichever is lower.

Effective CaF2 content	Base price per short ton
70 percent or more65 percent but less than 70 percent	\$28. 00 27. 00
60 percent but less than 65 percent Less than 60 percent	_ 26. 00

(2) The maximum price f.o.b. a producer's railroad or waterway shipping point shall be his maximum delivered price as determined under subparagraph (1) less freight from such shipping point to the consumer's plant.

(3) The effective CaF<sub>2</sub> content shall be determined by deducting 2½ times

the SiO<sub>2</sub> content from the CaF<sub>2</sub> content.

(b) Acid-grade fluorspar produced outside the Illinois-Kentucky fluorspar district. (1) The maximum price f.o.b. a consumer's plant for any shipment of acid-grade fluorspar with a minimum of 97½ percent CaF<sub>2</sub> and a maximum of ½ percent SiO<sub>2</sub> shall be \$32.00 per ton, plus either (i) railroad freight on such shipment from the seller's shipping point to the consumer's plant or (ii) railroad freight on such a shipment from Rosiclare, Ill., to the consumer's plant, whichever is lower.

(2) The maximum price f.o.b. a producer's railroad or waterway shipping point for such acid-grade fluorspar shall be his maximum delivered price as determined under subparagraph (1) less freight from such shipping point to the

consumer's plant.

The Office of Price Administration on November 28, 1942, exempted fluorspar ore (milling grade) from price control in Amendment No. 42 to Supplementary Regulation No. 1 to the General Maximum Price Regulation, effective November 23, 1942. Ceiling prices previously were the highest charged during March 1942.

## STOCKS AT MINES OR SHIPPING POINTS

According to reports of producers, the quantity of fluorspar in stock at mines or shipping points at the close of 1942 totaled 51,610 tons, or 29 percent less than in 1941. These stocks comprised 19,429 tons of finished fluorspar and 32,181 tons of crude fluorspar (calculated to be equivalent to 14,000 tons of finished fluorspar).

Stocks of fluorspar at mines or shipping points in the United States, December 31, 1941 and 1942, by States, in short tons

		1941		1942			
State	Crude 1	Finished	Total	Crude 1	Finished	Total	
Arizona California Colorado Illinois Kentucky New Mexico Texas	30 150 666 23,711 12,579 2,539	434 19, 966 10, 981 425 43	30 150 1, 100 43, 677 23, 560 2, 964 43	30 150 3,601 10,521 1,774 15,605	1,067 13,984 3,970 312	30 150 4, 668 24, 505 5, 744 15, 917	
Utah Washington	525	110 38	635 38	500	96	596	
	40, 200	31, 997	72, 197	32, 181	19, 429	51, 610	

<sup>1</sup> The greater part of this crude (run-of-mine) fluorspar must be beneficiated before it can be marketed.

#### TECHNOLOGIC DEVELOPMENTS

To meet the large and increasing demand for acid-grade fluorspar, several new flotation plants were completed during 1942, the capacity of some existing plants was enlarged, and two new plants were being constructed. New plants were completed and put into operation near Jamestown, Colo., by Harry M. Williamson & Son and the General Chemical Co.; near Salida, Colo., by the Fluorspar Processing Co. and Kramer Mines (Inc.); and at Elizabethtown, Ill., by James W. Patton & Sons. Near Smithland, Ky., Butler & Moodie added a 3-cell flotation machine to its milling plant. The flotation plants of the Aluminum Ore Co. and Rosiclare Lead & Fluor Spar Mining Co. at Rosiclare, Ill., of the Indian Metals Co. at Lordsburg, N. Mex., and of P. L. Grattan at Deming, N. Mex., were enlarged. New plants were being constructed at Los Lunas, N. Mex., by the Zuñi Milling Co., and near Marion, Ky., by the Corod Minerals Co. Output of flotation concentrates gained phenomenally in 1942,

amounting to 106,974 short tons compared with 64,627 tons in 1941. Experimental work was done on the Heavy-Media Process for separating fluorspar from gangue material. This work proved encouraging, and the installation will be made by the Rosiclare Lead & Fluor Spar Mining Co. in 1943. In applying this process ferrosilicon is used as the heavy medium. The Mahoning Mining Co. is adding to its flotation plant, enabling the company to mill high-barite ore.

# FLUORSPAR INDUSTRY IN 1942, BY STATES

Arizona.—Production in Arizona came from mines and prospects in Greenlee and Pima Counties; that from Greenlee County was shipped to flotation plants at Deming and Lordsburg, N. Mex. The flotation concentrates recovered from the fluorspar, rather than the run-of-mine material, have been credited in the statistics to Arizona. The fluorspar from Pima County was produced at the Fluxore

Claims by N. A. Gonzales and shipped to steel plants and iron foundries on the West coast. The property discontinued operating in April 1942.

California.—The Industrial Minerals & Chemical Co. shipped a small quantity of ground fluorspar during 1942. This company has a plant at West Berkeley, where fluorspar from Nevada is ground.

The fluorspar is credited in the statistics to Nevada.

Colorado.—The reopening of mines in Boulder and Jackson Counties and greatly accelerated production at mines in Chaffee County are reflected in the shipment of 31,743 short tons of fluorspar from Colorado in 1942 compared with 15,566 tons in 1941. Shipments in 1942, however, were 17 percent less than the all-time high established by Colorado in 1918. Of the 1942 shipments, 56 percent went to steel plants, 30 percent to hydrofluoric-acid plants, 8 percent to glass and enamel plants, and the remaining 6 percent to iron foundries, welding-rod manufacturers, and aluminum, magnesium, ferro-alloy, and cement plants.

Production in Colorado in 1942, which amounted to 33,400 tons, came from Boulder, Chaffee, Jackson, and Mineral Counties, but

mines in Chaffee County supplied 47 percent of the State total.

The flotation mill of Harry M. Williamson & Son near Jamestown made its initial production of concentrates in March 1942; the ore treated in the mill came from the company Emmett mine in Boulder County. At its Brown Sparmine, also in Boulder County, the shaft was sunk to 300 feet and a heavier hoist installed. The General Chemical Co., which acquired the Chancellor, Yellow Girl, and Burlington mines in Boulder County in 1940, acquired the Alice mine, also in Boulder County, in 1942. These mines furnish ore for the company flotation mill near Jamestown, which began production in May 1942. This company also operates a flotation mill in New Mexico. The American Fluorspar Corporation made a substantial increase in production at its mine near Salida (Chaffee County), did considerable development work, electrified the mine, and began opening a mine at Poncha Springs in the same county. The flotation mill of the Fluorspar Processing Co., on property of the American Fluorspar Corporation, began operating in April 1942; the ore milled is supplied by the American Fluorspar Corporation. The Colorado Fluorspar Corporation reported gains over 1941 of 24 and 86 percent, respectively, in production of metallurgical-grade and flotation concentrates. A shaft was sunk to the 118-foot level, and a 100-foot tunnel was driven along a newly found ore body. The flotation mill of Kramer Mines, Inc., near Salida, began operating in October 1942. Ore for the mill comes from the company mine, also near Salida. The Western Feldspar Milling Co., Denver, shipped 8 percent more ground fluor-spar to the glass trade in 1942 than in 1941. The ore ground by this company is supplied by the American Fluorspar Corporation. Western Fluorspar Corporation spent the latter part of 1941 and the first half of 1942 rehabilitating the long-idle mine near Northgate, Jackson County, and remodeling and enlarging the mill. Production was begun on July 15, 1942, and continued until December 10, when a fire destroyed the mill; it is now being rebuilt. The Wagon Wheel Gap mine, of the Colorado Fuel & Iron Corporation in Mineral County, was inactive in October because the concentrating mill was being remodeled; in consequence, production was 8 percent less than in 1941.

Illinois.—Approximately 282,000 short tons of fluorspar-bearing material, equivalent to 145,000 tons of finished fluorspar, were mined in 1942 compared with 248,000 tons, equivalent to 135,000 tons of finished fluorspar, in 1941. Of the finished fluorspar produced in 1942, it is estimated that about three-fifths was from vein deposits and two-fifths from bedded deposits. Of the fluorpsar produced in Illinois in 1942, about 95 percent came from Hardin County and

5 percent from Pope County.

Fluorspar-bearing material milled in 1942 totaled 296,000 tons. from which about 156,000 tons of finished fluorspar were recovereda ratio of 1.9:1. Considerable Kentucky fluorspar is milled in Illinois, and some Illinois fluorspar is milled in Kentucky; the finished fluorspar so recovered, as well as that shipped, is credited in the statis-

tics to the State of origin.

Shipments from Illinois (161,949 tons) in 1942, which established a new record, were 21 percent more than in 1941 and 3.4 percent greater than in 1917, the previous record year. The 1942 shipments comprised 77.947 tons to steel plants, 62,573 tons to hydrofluoric-acid plants, 7,520 tons to glass and enamel plants, 7,155 tons to Canada and Peru, and 6,754 tons to iron foundries, nonferrous smelters, aluminum- and magnesium-reduction plants, and ferro-alloy, nickel, and welding-rod manufacturers. Of the 1942 total, 42,250 tons were shipped by river or river-rail to consumers compared with 39.918 tons in 1941.

The Air Shaft-Midway-North Boundary, Argo, Blue Diggings, Crystal, A. L. Davis, W. L. Davis, Deardorff, W. C. Green, Hillside, Humm, Lead Hill, North Daisy, Roberts, Rosiclare, Stewart, and Victory mines supplied about 87 percent of the total finished fluorspar produced in Illinois in 1942; the remainder came from many mines and prospects, including the Austin, Big Creek, Cave in Rock, Cooper, Crabb, Douglas, Du Bois, Eureka No. 4 and No. 5, Good Hope, Hamp, Hanson, J. W. Hill, Last Chance, Lost 40, Love, Pell,

Red Tipple, Rose Creek, South Boundary, Wall, and Winn.
The Fluorspar Products Co. operated the Lead Hill and Stewart mines and also milled purchased ore from various properties. Shipments were 8 percent less than in 1941. Two shafts were sunk on the Stewart property. A core drill was operated about 9 months.

The Aluminum Ore Co. produced 95 percent more fluorspar at its flotation plant in 1942 than in 1941. The mill feed comprised ore from the company Argo, Blue Diggings, Good Hope, Hamp, Hanson, and Last Chance mines and a small quantity of purchased ore. Additional flotation cells and drying and grinding equipment were added to the mill in 1942, doubling its capacity. The company was active sinking shafts in 1942. Its Fairview shaft, on the Argo-Blue Diggings veins, has been sunk to the 700-foot level; it is being sunk an additional 90 feet and will be the largest shaft in the fluorspar district, being 12 by 12 feet cross section in the clear. Three smaller shafts have been sunk along the same veins to the 300-foot level; these shafts were required to supply the immediate demand for crude material, and each was brought into production during the latter part of 1942.

Production at the Crystal mine of the Crystal Fluorspar Co. was slightly less than in 1941. Considerable output was lost as a result of two strikes. Prospecting and development work included 17,211 feet of churn and diamond drilling at the Crystal mine and 935 feet of churn drilling along the Crystal-Mahoning east-west property line. Hillside Fluor Spar Mines purchased the Dimick property, adjoining the Hillside property on the northwest, and has rehabilitated the shaft to the 200-foot level. Workings are being carried forward on two prominent ore bodies to develop them for production. Exploration work is being done by drilling in cooperation with the Illinois Geological Survey, which also has been doing some geophysical work. Production of gravel fluorspar and flotation concentrates by Hillside Fluor Spar Mines was 7 and 4 percent, respectively, less than in 1941. The mill feed came from the Dimick, Hillside, and Wall mines in

Illinois and the Keystone mine near Marion, Ky.

The Rosiclare Lead & Fluor Spar Mining Co. operated the Daisy, Eureka No. 4 and No. 5, Midway-North Boundary-Air Shaft, North Daisy, Rosiclare, and South Boundary mines in 1942, but the North Boundary and Rosiclare mines were the chief producers. Production at the gravity concentrating mill was 5 percent less than in 1941. Output at the flotation plant, however, was 89 percent more than in 1941. Shipments of fluorspar of all grades were 33 percent greater than in 1941. The flotation mill was enlarged during 1942. Experimental work was done on the Heavy-Media Process for separating fluorspar from gangue material. This work proved encouraging, and the installation will be made in 1943. In applying this process ferrosilicon is used as the heavy medium. The company pushed development work in all its mines and did considerable surface and underground drilling. Development work was under way on the 600- and 700-foot levels of the Rosiclare mine, and considerable prospecting was done on an outlying property.

The Victory mine of the Victory Fluorspar Mining Co. was operated at about the same rate as in 1941. A diamond-drilling program was carried on during the summer and fall without any notable finds.

The Cave in Rock Spar Co. remodeled its mill and did some development work at its mining properties. Most of the ore milled in 1942 was purchased from local producers. Production of finished fluorspar,

however, was substantially less than in 1941.

The flotation mill of the Mahoning Mining Co. produced 28 percent more fluorspar concentrates than in 1941. The mill feed comprised ore from the A. L. Davis, W. L. Davis, Deardorff, and W. C. Green mines and a small quantity of purchased ore. Production of finished fluorspar comprised 86.4 percent acid grade and 13.6 percent pelletized gravel. During 1942 a new shaft (the East Green) was completed to develop an ore body, and the A. L. Davis and West Green ore bodies were opened. At the flotation plant, improvements are in progress to enable the mill to handle high-barite ore and to increase capacity to some extent. The motors in the flotation mill 3 and the new Diesel generating unit at the W. L. Davis mine 4 have been described by Edwards.

Jas. W. Patton & Sons treated tailings from the Crystal mine in

its flotation plant near Elizabethtown.

The Humm mine was operated by C. C. Mackey during the first 9 months of 1942, then it was worked by Barnett, Karber & Adams. Output by all operators was at about the same rate as in 1941.

The Yingling Mining Co. did considerable development work and produced a small quantity of fluorspar at the Nicholas Hamp and

<sup>&</sup>lt;sup>3</sup> Euwards, J. H., Some Electrical Aspects of a New Fluorspar Plant: Eng. and Min. Jour., vol. 143, No. 3, March 1942, pp. 56-58.

<sup>4</sup> Edwards, J. H., Mahoning's New Diesel Unit Generates 240 Volts A. C.: Eng. and Min. Jour., vol. 143, No. 4, April 1942, p. 55.

THE RESIDENCE OF THE PARTY OF T

Rose Creek mines. It remodeled a mill formerly run by the Big Creek Fluorspar Co., which discontinued operations in March 1942. The mill includes air tables and electrostatic separation to produce fluorspar, lead, and zinc concentrates.

A new operator, the Minerva Oil Co., is developing a mine near Cave in Rock and expects to get into production the latter part of 1943. A shaft is being sunk to a depth of 630 feet, and a flotation plant

to produce fluorspar and zinc concentrates is planned.

Production at the Roberts mine in Pope County, operated by Roberts & Frazer of Illinois (Kentucky Fluor Spar Co. affiliate) more than tripled that in 1941. This mine is equipped with log washer,

picking belt, and screens.

Kentucky.—Production of fluorspar (expressed in terms of finished product) in Kentucky was about 121,500 short tons in 1942 compared with 135,500 tons in 1941. Shipments were 134,133 tons in 1942, a decline of 6 percent from the all-time record of 1941. The 1942 shipments comprised 111,370 tons to steel plants, 11,141 tons to glass and enamel plants, 4,576 tons to hydrofluoric-acid plants, 1,750 tons to Canada, and 5,296 tons to iron foundries, nonferrous smelters, and cement, ferro-alloy, and aluminum-reduction plants. Of the 1942 total, 36,799 tons were shipped to consumers by river or river-rail compared with 34,698 tons in 1941.

Production in Caldwell County came chiefly from the Hollowell &

Hobby, Hughett, Marble, Senator, and Tyrie (Lester) mines.

John Hughett completed a shaft at his mine near Princeton and

began production in 1942.

Production at the Hollowell & Hobby mine, operated by the New York & Kentucky Mining Co., was about 25 percent less than in 1941. The company did much prospecting but did not locate any extensive ore bodies.

Core drilling by W. H. Crider disclosed a productive ore body at the Senator mine, and a shaft was sunk and machinery installed. The mine was sold to the Midland Minerals Corporation in December 1942.

Various operators produced fluorspar at the Marble mine of the S. L.

Crook Corporation during 1942.

About 90 percent of the production in Crittenden County came from the Bachelor, Davenport, Keystone, Pigmy, Summers, Tabb, Waddell, and Watson (Eagle) mines. Most of the remainder came from many smaller mines (including the Barnes, Blue, Brown, Butler, Corn, Crystal, Dyke, Gilless, Haffaw, Hodge, Krause, Madry, Memphis, Pogue, Redd, Reiter, Simpkins, Sullinger, and Watkins) and from numerous prospects; some was reclaimed from waste dumps and old workings of abandoned mines.

The Eagle Fluor Spar Co. produced 17 percent more fluorspar at its Watson mine than in 1941. The 1942 production comprised 74 percent of metallurgical grade and 26 percent of acid grade. Perry & Loyd reworked the Watson tailings and recovered considerable

fluorspar.

The mill of R. J. Forester handled ore from his Summers mine and some purchased ore, recovering about the same quantity of finished

fluorspar as in 1941.

The Tabb mines and mill of the United States Coal & Coke Co. produced 8 percent more finished fluorspar than in 1941; shipments were 40 percent greater. The company did considerable development work and made improvements in its mill during 1942.

The Kentucky Fluor Spar Co., which operates a mill a short distance south of Marion, did the largest volume of business in its history; tonnage and dollar sales were 14 and 31 percent, respectively, greater than in 1941. In 1942 the company, through its mining division (Roberts & Frazer), operated the C. R. Babb, Carr, and Ellis mines in Livingston County, Ky., and the Roberts mine in Pope County, Ill.; about two-thirds of the company supply came from these mines, and the remainder chiefly from the Barnes, Nancy Hanks, and

Waddell mines in Kentucky.

At the Keystone mine of Hillside Fluor Spar Mines a new deep-well pump, operated by direct-connected Diesel engine and capable of handling 1,000 gallons of water a minute against a 600-foot head, was installed in 1942. With this equipment it is hoped to keep the lower levels unwatered during the heavy-rain season and to extend the workings at least to the 600-foot level. A new shaft (No. 4) was sunk to 300 feet and encountered good ore. The workings of this shaft will be connected with other mine workings to the north to give additional tramming and hoisting facilities. Production at the Keystone mine was considerably less than in 1941. Although the fluor-spar from this mine is finished at the company mill at Rosiclare, Ill., production and shipments are credited in the statistics to Kentucky.

Production at the Pigmy mine of the Pigmy Corporation (subsidiary of the Rosiclare Lead & Fluor Spar Mining Co.) was 19 percent less than in 1941. Development work at the Pigmy mine consisted

chiefly of shaft sinking, drifting, and diamond drilling.

Development work at the Davenport mine consisted of locating an unknown ore body by drilling and of driving a crosscut to it. A new shaft to cut the extension of this ore body is contemplated. A new 6-cell coarse jig was added to the mill. Production was about 21 percent less than in 1941. The mineral right and some surface at the Davenport mine were purchased December 31, 1942, by the National Fluorspar Co., which previously operated the mine under lease.

In 1942 the Delhi Fluorspar Corporation continued development work at its Bachelor mine and plans to sink a 600-foot shaft in early 1943. Production was substantially less than in 1941. However, the 1942 deficit in production was made up with purchased fluorspar; as a consequence, shipments from Kentucky were greater than in 1941.

The Howard Easley Corporation, which operates a custom mill near Marion, worked two shifts during part of 1942 and as a result milled considerably more ore than in 1941. In the mill a second crusher was added and many improvements were made to increase production.

In Livingston County the bulk of the fluorspar produced came from the C. R. Babb, Carr, Ellis, Nancy Hanks, and Wright mines, from C. R. Babb and Nancy Hanks tailings, and from the jig reclaiming

plant working Klondike tailings.

Output at the C. R. Babb, Carr, and Ellis mines of Roberts & Frazer was 31 percent greater than in 1941. Edwin W. Frazer reworked the tailings at the C. R. Babb mine and recovered 380 tons

of fluorspar.

The levels in the Nancy Hanks mine, operated by W. V. Haynes, Jr., were retimbered during 1942, causing some loss in production. Nevertheless, output of finished fluorspar was 7 percent more than in 1941. Tinsley & Loyd reclaimed a substantial quantity of fluorspar from Nancy Hanks tailings.

Butler & Moodie, operating a jig plant reclaiming fluorspar from Klondike-mine tailings, recovered about half as much fluorspar from that source as in 1941. Some ore was also milled for John Hughett.

A 3-cell flotation machine was installed during January 1943.

As the result of an increase in price and a change in the specification for metallurgical-grade fluorspar, Ralph E. Jones has reopened the Faircloth mine in Woodford County near Wilmore and has remodeled the mill. The ore in this mine is impregnated with considerable calcite and is difficult to mill to 85 percent calcium fluoride. However, it is associated with but little silica and is therefore amenable to a product containing 70 percent effective calcium fluoride. A small production was made in 1942.

Nevada.—Shipments of fluorspar from Nevada in 1942—8,020 short tons—were 11 percent less than the all-time record of 8,967 tons in 1941. Most of the 1942 total went to steel mills and hydrofluoric-acid

plants.

The chief producing mine in Nevada in 1942 was the Baxter in Mineral County, operated by V. S. Baxter; production was about the same as in 1941. The other active mine was the Daisy in Nye County, operated by J. Irving Crowell, Jr.; production was 25 percent less than in 1941.

New Mexico.—Production of fluorspar in New Mexico, which established a new record in 1942, came from Catron, Dona Ana, Grant,

Luna, Sierra, and Valencia Counties.

Shipments from New Mexico, Arizona, and Texas totaled 23,291 short tons compared with 19,089 tons in 1941. Of the 1942 shipments, slightly more than half was of metallurgical grade, which moved to steel mills and iron foundries; the remainder was chiefly flotation concentrates, which were shipped mainly to hydrofluoric-acid and glass plants.

The gravity-flotation mill of the Non-Metallic Corporation at Silver City was operated by the Continental Chemical & Ore Co. during part of 1942; the concentrates produced were shipped to a hydrofluoric-acid plant. The mill feed comprised chiefly purchased ore from the Clum mine in Grant County; a small amount came from the Huckleberry mine in Catron County, operated by the company.

The Diamond mine (formerly Tortugas) near Mesilla Park, Dona Ana County, is being reopened by Jacques K. Stanland. The shaft was extended 300 feet farther, about 1,500 feet of lateral work were done, a railroad connection was built to the mine, and a gravity-concentration mill was expected to be completed in early spring. In the course of development work, some milling-grade ore was

produced and shipped to a local flotation plant.

The flotation mill of the Indian Metals Co. at Lordsburg was operated at a substantially reduced rate in 1942. The ore milled was purchased from many properties, but the greater part came from the Howard and Sanders mines in New Mexico and the Ellis (Fourth of July No. 2) mine in Arizona. The Indian Metals Co. practically rebuilt its mill, doubling capacity, in 1942, recently began development work at two mines in Hidalgo County, and plans to develop two additional mines in the same county.

P. L. Grattan's remodeled flotation mill at Deming resumed production in 1942. A new bank of cells was added, and changes and improvements were also made. At the Grattan mine in Luna County

the shaft was straightened, and a head frame, surface houses, and a road were built.

The Lucky and Greenleaf No. 4 mines in Luna County have been under development since October 1942 by the Western Mining Corporation. The Lucky mine made its initial production in January 1943.

The Howard and Sadler mines in Luna County were important

producers during 1942.

The flotation mill of the General Chemical Co. at Deming was operated on a substantially larger scale than in 1941. This company also operated the Spar Group and Sadler mines in Luna County and the Osmer (Shrine) mine in Grant County; the last two mines were acquired in 1942. In addition to the production from its own mines, considerable milling-grade ore was purchased from various producers

in Arizona, New Mexico, and Texas.

Since May 1942 Kinetic Chemicals, Inc. (du Pont subsidiary), has carried on development work at its Lyda K mine near Arrey, Sierra County. As of December 31, a new 100-foot shaft had been sunk at the north end of the vein, and a 150-foot drift to the northeast and a 175-foot drift to the southwest had been driven at that level. A new hand-sorting mill, under construction, is expected to be in operation by April 1943 at an annual rate of 10,000 tons. Production is expected to comprise about 15 percent of acid grade, 50 percent of metallurgical grade, and 35 percent of mill-feed grade.

The Navajo mine in Valencia County, operated by Navajo Fluorspar Mines, produced 65 percent more finished fluorspar than in 1941. In addition, a substantial tonnage of ore was produced for mill feed at the flotation mill being constructed at Los Lunas (N. Mex.) by the Zuni Milling Co., affiliate of Navajo Fluorspar Mines. This mill is

expected to be brought into production during 1943.

Development work was done and considerable fluorspar produced during 1942 at the Bonita and Breece mines in Valencia County by the Both Mining & Milling Co.

Small outputs were made at the Mirabal and Keeney properties,

also in Valencia County.

Tennessee.—The Foley mine in Smith County near Rome was reopened in 1942 and a small quantity of metallurgical-grade fluorspar was produced and shipped by Frailey & Heap.

Texas.—A small tonnage of milling-grade ore was produced at the Horse Shoe prospect near Hot Wells, Hudspeth County, by U. B. Melton; it was shipped to a flotation plant at Deming, N. Mex.

Utah.—Shipments of fluorspar from Utah in 1942 were 1,018 short

tons (an all-time high) compared with 748 tons in 1941.

The Western Fluorite Co., which has done considerable development work at many properties in Beaver County and completed a mill near Milford, was the chief producer in Utah in 1942. The Staats mine, also in Beaver County, operated by Fred Staats, produced substantially less fluorspar than in 1941, chiefly because of a shortage of labor.

The Cougar mine near Milford in Beaver County was being devel-

oped by the Tintic Standard Mining Co. in 1942.

Washington.—A small quantity of fluorspar, mined in 1941, was shipped from the Mitchem mine in Ferry County by the Mineral Products Co. in 1942.

#### FOREIGN TRADE

Imports.—Imports of fluorspar for consumption in the United States during 1942 were 2,151 short tons (1,882 tons containing more than 97 percent and 269 tons containing not more than 97 percent calcium fluoride), valued 5 at \$35,529, compared with 7,524 tons (1,516 tons containing more than and 6,008 tons not more than 97 percent calcium fluoride), valued 5 at \$80,135. The value assigned to the higher-grade foreign fluorspar averaged \$19.69 and \$16.98, respectively, in 1941 and 1942, and that of the lower-grade \$8.37 and \$13.30, respectively. The cost to consumers in the United States also includes duty, loading charges, insurance, consular fee, and freight to consuming plants.

Fluorspar imported for consumption in the United States, 1941-42, by countries 1 and customs districts

Country and customs district	Containir than 97 calcium	ng more 7 percent 1 fluoride	Containir more percent fluoride	than 97 calcium	To	tal
grimen e (1882) e Heitzer Hersterijal e Grigorija e Heitze	Short	Value	Short tons	Value	Short tons	Value
Mexico:						
Laredo	68	\$863	1,621	\$14,704	68 1,621	\$863 14, 704
New York Philadelphia	1,448	28, 987	1, 315	12,777	1, 448 1, 315	28, 987 12, 777
Spain: PhiladelphiaUnited Kingdom: Rochester	1, 516	29, 850	2, 936 3, 070 2	27, 481 22, 772 32	4, 452 3, 070 2	57, 331 22, 772 32
ing manganga balan janung kalungga Subar Subar Subar Jaka Subar Baraga Subar	1,516	29, 850	6,008	50, 285	7, 524	80, 135
1942 Canada: St. Lawrence			(2)	10	(2)	10
Mexico: El Paso Laredo New York Philadelphia	483 92 1,077 230	6, 860 605 20, 541 3, 945	1 268	12 3, 556	484 360 1,077 230	6, 872 4, 161 20, 541 3, 945
	1,882	31, 951	269	3, 568	2, 151	35, 519
	1,882	31, 951	269	3, 578	2, 151	35, 529

<sup>&</sup>lt;sup>1</sup> For historic table, see Minerals Yearbook, 1941, p. 1401. <sup>2</sup> Less than 1 ton.

The following table, compiled from data furnished to the Bureau of Mines by importers, shows the quantities of imported fluorspar delivered to consumers in the United States in 1941 and 1942 and the selling price at tidewater (duty paid), irrespective of the year of importation into the United States; it differs from the preceding table, which shows the quantities received in the United States during 1941 and 1942. The quantities in the following table are based upon the actual outturn weights ascertained by sworn weighers and represent the weights on which duty was paid and entries were liquidated.

<sup>\*</sup> As defined in sec. 402 of the tariffact of 1930, "The value of imported merchandise \* \* \* is the foreign value or the export value, whichever is higher—that is, the market value or the price at which the merchandise, at the time of exportation to the United States, is offered for sale in the principal markets of the country from which exported, including the cost of containers or coverings and all expenses (including any export tax) incident to placing the merchandise in condition ready for shipment to the United States."

Imported fluorspar delivered to consumers in the United States, 1941-42, by uses

		1941			1942	
Use	Short tons Selling price at tide-water, including duty		Short tons	Selling price at tide- water, including duty		
		Total	Average		Total	Average
Steel Hydrofluoric acid Miscellaneous	6, 102 1, 418 69	\$143 863 38, 760 1, 380	\$23. 58 27. 33 20. 00	269 1, 900	<sup>1</sup> \$6, 700 53, 500	1 \$24, 91 28, 16
	7, 589	184, 003	24. 25	2, 169	60, 200	27. 75

<sup>&</sup>lt;sup>1</sup> Estimated.

Exports.—Producers of fluorspar reported exports of 9,016 short tons of fluorspar valued at \$242,545 in 1942 compared with 12,184 tons valued at \$277,782 in 1941. The exports in 1942 by producers comprised 1,714 tons of fluxing gravel, 557 tons of ceramic ground, 4,899 tons of acid grade, and 1,616 tons of special-grade (96 percent CaF<sub>2</sub>) jig concentrates, all to Canada, and 230 tons of ceramic ground to Peru. In addition to the fluorspar exported by producers in 1942, brokers reported exports of 4 tons of ceramic ground—3 to Chile and 1 to Uruguay.

Fluorspar reported by producers as exported from the United States, 1938-42

Year	Short tons	Va	lue	Year	Ob4 4	Va	lue
1641	BHOLL TOHS	Total	Average	I ear	Short tons	Total	Average
1938 1939 1940	788 2, 976 8, 482	\$9,061 74,443 178,467	\$11.50 25.01 21.04	1941 1942	12, 184 9, 016	\$277, 782 242, 545	\$22, 80 26, 90

Tariff reduction.—The trade agreement between the United States and Mexico, signed December 23, 1942, and proclaimed by the President December 28, provided for a duty of \$6.30 a long ton (\$5.625 a short ton) on fluorspar containing not more than 97 percent calcium fluoride imported into the United States. The former duty was \$8.40 a long ton (\$7.50 a short ton). The duty on fluorspar containing more than 97 percent calcium fluoride remained at \$4.20 a long ton (\$3.75 a short ton).

#### WORLD PRODUCTION

The following table shows world production of fluorspar by countries from 1937 to 1942, insofar as statistics are available. Because of restriction on the publication of statistics by the governments of many countries, few figures for 1940, 1941, and 1942 are available.

World production of fluorspar, 1937-42, by countries, in metric tons 1

[Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
Argentina (shipments)	350	1,406	739	597	2, 027	(2)
Australia:			/as	(2)	(2)	(2)
New South Wales	_ 55 4		(2)	(2) (2) (3) (2)	(2) (2) (2) (3)	(2) (2) (2)
Queensland South Australia	1,410	2,479	20	(2)	(2)	(3)
South Australia				(2)	(2)	(2)
Victoria		804		(4)	(9)	(4)
Canada	_ 136	197	218	4,041	5,020	3, 624
Chosen	_1 11.000	3 34, 207	(2) (2)	(2) (2)	(2) (2)	(2) (2)
France	51, 430	51,920	(2)	(2)	(2)	(2)-
Anhalt	13,662	10,462	(2)	(2)	(2)	(2)
Baden	13,637	21,350	(2)	(2)	(2)	(2)
Bavaria	62, 455	59, 919	(2)	(2)	(2)	(2)
Descrio	30 514	22, 956	(2) (2) (2) (2) (2) (2)	(2) (2) (3) (2) (3) (4)	000000	3 3 3 3 3 3
Saxony	8,074	12,063	(2)	(2)	(2)	(2)
Thuringia	16, 117	22, 405	25	(2)	(2)	(2)
India, British	- 20, 22.	,	`´20	(2)	(2)	(2)
		12, 186	(2) T	(2)	(2)	(2)
Italy	8, 479	8,944	11, 227	14, 697	11.581	4 32 660
Newfoundland (shipments)	1,692	1,676	2, 367	(2)		(2)
Norway Southern Rhodesia	- 1,002	1,010	2,001	(2)	25	25
Southern Knodesia		585	105	2	2	/25
South-West Africa	4, 250	8,596	(2)	(2) (2) (2)	(2) (2) (2) (3) (2)	(2) (2) (2) (2) (2) (2) (3) (4)
Spain		2,060	2, 473	- X	1 2	1 %
Tunisia	1,676	2,000	10, 322	7, 421	4 3, 900	1 2 507
Union of South Africa	3, 615	4,736	10, 322			(3), 021
U. S. S. R.	- 10,000	(6)	(2)	(3)	(2)	(2)
United Kingdom	42,837	33,866	7 17, 521	011	000000	200 071
United States (shipments)	_ 164, 408	72, 940	165, 806	211, 917	290, 905	326, 871
and the state of the state of the	519,000	456,000	(2)	(2)	(2)	(2)

<sup>&</sup>lt;sup>1</sup>In addition to countries listed, China and Mexico produce fluorspar but data of output are not available.

<sup>2</sup> Data not available.

Exports.
Estimated.

January to September, inclusive.
Estimate included in total.

7 January to June, inclusive.

Argentina.—Production of fluorspar in Argentina increased markedly to 2,234 short tons in 1941 from 658 tons in 1940.

Brazil.6—The Companhia Brasileira de Alumino controls a promising, newly discovered fluorspar deposit in the southern edge of the sulfide belt of Ribeira de Iguapa Valley. Before this discovery, only

minor occurrences of fluorspar were known in the country.

Canada.—Production of fluorspar in Canada has been relatively small in recent years but in 1941 amounted to 5,534 short tons. This output, however, falls far short of consumption; consequently, search for deposits has been under way. The greater part of the fluorspar consumed in Canada is imported from Newfoundland and the United States.

Mexico.—Production figures on fluorspar in Mexico in 1942 are not available, but 5,914 short tons were exported in that year compared with exports of 11,597 tons in 1941 and 10,220 tons in 1940. Most of the fluorspar exported in 1940 and 1941 went to Japan. Before the war the La Azul mine at Taxco, Guerrero, largest producer of fluorspar in Mexico, was under Japanese control; it has since been taken over by the Enemy Property Custodian, who has called for bids to operate the mine. When production is resumed, a substantial increase in output can be expected.

<sup>6</sup> Engineering and Mining Journal, vol. 143, No. 6, June 1942, p. 105.

Newfoundland.—Production of fluorspar in Newfoundland in 1942 is reported to have reached 36,000 short tons.7 Efforts are being made to increase this output, and it is hoped that production in 1943 will

reach 100,000 tons.

Fluorspar is produced in Newfoundland by the St. Lawrence Corporation of Newfoundland, Ltd., and Newfoundland Fluorspar, Ltd., the latter a subsidiary of the Aluminum Co. of Canada, Ltd. Production and shipments by the St. Lawrence Corporation of Newfoundland, Ltd., were 12 and 9 percent, respectively, greater in 1942 The 1942 shipments went to Canadian consumers and than in 1941. comprised 15 percent acid grade, 74 percent metallurgical grade, and 11 percent crude (65 percent CaF<sub>2</sub>). The St. Lawrence Corporation of Newfoundland, Ltd., completed a flotation plant late in 1942. Newfoundland Fluorspar, Ltd., which has been doing exploration and development work for several years, began producing in 1942. hand-picking and crushing at the mine the output, which contains 70 to 80 percent calcium fluoride, is shipped to Arvida, Canada, where the Aluminum Co. of Canada, Ltd., has a flotation plant to mill the ore to acid grade.

Sweden.—For some time explorations have been made regarding possibilities of mining fluorspar at the Branteviks mines in the Province of Skåne in south Sweden. Deposits were discovered near the surface, and test borings have now reached a depth of 50 to 60 meters (164 to 197 feet). Machinery to permit further operations has

been ordered.8

Aktiebolaget Branteviks Gruvor has begun mining fluorspar on a small scale; the material is to be used in manufacturing light metals

in a plant at Sundsvall.9

Union of South Africa.—Production of fluorspar in the Union of South Africa was 3,888 short tons during the first 9 months of 1942 (figures for the remaining 3 months not available) compared with about 4,300 tons in the year 1941 and 8,180 tons in 1940.

#### CRYOLITE

Cryolite occurs in commercial quantity and is mined at only one place-Ivigtut, Greenland. Gibbs 10 has described the mine at Ivigtut, grades of ore produced, methods of processing and purification, and various uses of cryolite.

A sizable proportion of the cryolite used in the United States is ade from fluorspar. According to Frary: 11

made from fluorspar.

The fluorspar is treated with sulfuric acid to produce hydrofluoric acid, and this is neutralized with the proper amounts of soda ash and aluminum hydrate to produce the cryolite, which is a double fluoride of sodium and aluminum (Na<sub>3</sub>AlF<sub>6</sub>). The artificial cryolite is quite satisfactory and, in fact, considerably lower in objectionable impurities than the natural cryolite usually used. would be no serious difficulty in getting along with the artificial product if the supply of natural cryolite from Greenland is shut off.

The chief use of cryolite is in the metallurgy of aluminum; comparatively small amounts are used in glass, enamels, abrasives, and insecticides.

<sup>&</sup>lt;sup>7</sup> Cole, W. E., Jr., American vice consul, St. John's, Newfoundland, February 9, 1943.
<sup>8</sup> Klath, T. O., commercial attaché, Stockholm, Sweden, March 9, 1942.
<sup>9</sup> Chemical and Engineering News, vol. 20, No. 13, July 10, 1942, p. 858.
<sup>10</sup> Gibbs, A. E. (technical director, Pennsylvania Salt Manufacturing Co.), Cryolite as a Chemical Raw Material: Chem. Ind., vol. 38, May 1936, pp. 471-476.
<sup>11</sup> Frary, F. C., Cryolite from Fluorspar: Steel, vol. 108, No. 26, June 30, 1941, p. 4.

Cryolite was put under complete allocation and use control by General Preference Order M-198, issued by the War Production Board September 18, 1942. Cryolite, both natural and artificial, could not be delivered, received, or used after October 1, 1942, except by specific authorization of the War Production Board. The sole exception to the provision is receipt and use as an insecticide.


Artificial cryolite was manufactured in the United States in 1942 by the Aluminum Ore Co. at East St. Louis, Ill.; this company is building a plant near Bauxite, Ark. A small quantity of artificial cryolite was made in a pilot plant by the Pennsylvania Salt Manufacturing Co. in 1942; it has about completed a commercial plant at

Cornwells Heights, Pa.

The following table shows imports of cryolite into the United States in 1941 and 1942.

Cryolite (natural and artificial) imported for consumption in the United States, 1941-42, by countries

	19	41	1942		
Country	Long tons	Value	Long tons	Value	
Canada.	4	\$1, 125 1, 461, 600			
Greenland	26, 680	1, 461, 600	64, 565	\$3, 859, 875	
	26, 684	1, 462, 725	64, 565	3, 859, 875	



# **FELDSPAR**

By ROBERT W. METCALF

#### SUMMARY OUTLINE

	Page		Page
Summary	1413	Aplite	. 1419
Salient statistics	1413	Technologic developments	
Domestic production	_ 1414		
Crude feldspar	_ 1414	Other developments	1420
Ground feldspar		Imports	1421
Consumption and uses	. 1416		
Crude feldspar			
Ground feldspar		World production	1422
Manhalina arranita	1418	T to the second of the second	

# SUMMARY

Conversion of many enamel and porcelain plants to the heat treating of steel, to the manufacture of parts or assemblies for war machines, or to other activities more closely allied to successful completion of the war sharply reduced the consumption of feldspar in the enamel and porcelain industries in 1942. Curtailment of plate-glass production also tended to reduce feldspar sales. However, production and shipments of glass containers, which probably represent the most important consumer outlet for feldspar, in 1942 broke all records by increases of 12 and 15 percent, respectively, over 1941, the former record year. Sales of feldspar to glass plants in 1942 were the highest recorded since annual statistics by uses were first compiled (1934) and undoubtedly also the highest in the history of the industry. The 7-percent increase over 1941 in this category, however, was not sufficient to offset the decline in sales to porcelain and enamel manufacturers.

# Salient statistics of the feldspar industry in the United States, 1940-42

	1940	1941	1942	Percent of change in 1942
Crude feldspar:				
Domestic sales:	290, 763	338, 860	307, 823	_0 2
Long tons	\$1, 271, 995	\$1, 519, 456	\$1, 516, 791	-9.2 2
ValueAverage per long ton	\$4.37	\$4.48	\$4.93	+10.0
Imports:	420.	<b>V</b>	<b>*</b>	
Long tons	12, 522	11, 253	9, 525	15. 4
Value	\$80, 274	\$73, 236	\$69,797	-4.7
Average per long ton	\$6.41	\$6.51	\$7.33	+12.6
Ground feldspar sold by merchant mills:		i .	ł	
Short tons	285, 713	354, 417	327, 786	-7.5
Value	\$3,065,482	\$3, 782, 603	\$3, 524, 969	-6.8 +.7
Average per short ton	\$10.73	\$10.67	\$10.75	+.7

Sales of crude spar in 1942 totaled 307,823 long tons, valued at \$1,516,791, a decrease of 9 percent in quantity and of 0.2 percent in value from 1941. Sales of ground spar aggregated 327,786 short tons valued at \$3,524,969, a decline of about 7 percent in quantity and value from 1941. The output of both crude and ground feldspar in

1942, however, was considerably higher than in any year other than 1941. The average value per ton of crude spar rose 10 percent in 1942, while the downward trend in recent years in realization per ton of ground spar was checked and a small increase recorded.

Crude feldspar imported into the United States in 1942 amounted to 9,525 long tons valued at \$69,797, a decrease of 15 percent in tonnage and 5 percent in value from 11,253 tons valued at \$73,236

imported in 1941.

Most States produced somewhat less crude feldspar than in 1941, notable exceptions being Arizona, California, and Wyoming. In 1942 South Dakota achieved a new high in output (sales) of ground feldspar. Other States grinding more spar than in 1941 were Arizona, California, and Virginia. Somewhat smaller outputs than in 1941 were reported by New Jersey-Connecticut, North Carolina-Tennessee, Maine, and New Hampshire.

# DOMESTIC PRODUCTION

Following the usual practice in the industry, crude feldspar is reported in long tons of 2,240 pounds and ground feldspar in short

(net) tons of 2,000 pounds.

Crude feldspar.—Crude feldspar sold in 1942 totaled 307,823 long tons, a 9-percent decrease from the record year 1941 but 6 percent above sales in the highest previous year (1940). The total value (\$1,516,791) in 1942 was only slightly less than in 1941.

Crude feldspar sold or used by producers in the United States, 1938-42
[Value at mine or nearest shipping point]

Year	Tong tong	Value		Year Long tons		Val	ue
Tear	Long tons	Total	Average	rear	Long tons	Total ,	Average
1938 1939 1940	196, 119 253, 466 290, 763	\$895, 081 1, 112, 857 1, 271, 995	\$4. 56 4. 39 4. 37	1941 1942	338, 860 307, 823	\$1, 519, 456 1, 516, 791	- \$4.48 4.93

Crude feldspar sold or used by producers in the United States, 1940-42, by States
[Value at mine or nearest shipping point]

State	19	40	19	41	1942		
State	Long tons	Value	Long tons	Value	Long tons	Value	
Arizona California Colorado Connecticut Maine Maryland Massachusetts New Hampshire New York North Carolina Pennsylvania South Dakota Texas. Virginia Wyoming Undistributed 2	(1) 2, 711 34, 105 24, 404 18, 390 (1) 38, 589 (1) 79, 312 (1) 54, 692 21, 705 7, 833 9, 022 290, 763	(1) \$18, 254 123, 514 128, 348 84, 796 (1) 149, 031 (1) 426, 784 (1) 157, 323 116, 531 29, 128 38, 286 1, 271, 995	(1) 4, 464 42, 326 13, 693 22, 566 (1) 52, 219 (1) 100, 016 (1) 59, 015 (1) (1) 11, 846 32, 715	(1) \$22, 490 147, 640 92, 397 116, 610 (1) (2) 200, 569 (1) 552, 386 (1) 723 (1) (1) (2) 170, 723 (1) (1) 43, 484 173, 157	(1) 5,090 33,610 12,807 8,835 46,544 (1) 93,644 (1) 56,499 (1) 24,298 13,953 12,543	(1) \$23, 26 135, 56 92, 07 53, 14: 	

<sup>1</sup> Included under "Undistributed."

Includes States indicated by "(1)."

States producing crude feldspar in 1942 were the same as in 1941. except that no output in 1942 was reported from Maryland or Mas-The four leading States in 1942, in order of production-(North Carolina, South Dakota, New Hampshire, and Colorado), reported decreases of output ranging from 4 percent for South Dakota to 21 percent for Colorado. There were substantial percentage increases, however, in California, Virginia, and Wyoming, as well as in Arizona and Texas; production data cannot be shown for the last two. Sales of crude feldspar in 1942 in Connecticut, Maine, and New York were less than in 1941.

The average sales realization per long ton for crude feldspar increased 10 percent over 1941 to \$4.93 in 1942 and was the highest reported since 1937. All States for which figures can be given (except California and Wyoming) show higher average values in 1942 than in 1941. Averages per ton for selected States in both years (1941 in parentheses) follow: North Carolina, \$5.70 (\$5.52); Virginia, \$5.77 (\$5.58); South Dakota, \$3.46 (\$2.89); Maine, \$6.02 (\$5.17); and

Colorado, \$4.03 (\$3.49).

Ground feldspar.—Ground feldspar sold by merchant mills in 1942 decreased 8 percent in tonnage and 7 percent in value, compared with the peak year 1941, and totaled 327,786 short tons valued at \$3,524,969. The tonnage in 1942 was 15 percent above that in 1940, the former record year. Sales by North Carolina and Tennessee mills supplied 26 percent of the total ground spar sold, compared with 27 percent in 1941 and 1940 and 32 percent in 1937. Although producing slightly less ground spar in 1942 than in 1941, South Dakota and Colorado combined furnished 37 percent in 1942 compared with 34 percent in 1941 and 30 percent in 1937. Sales of feldspar of Canadian origin ground in United States mills amounted to 3 percent of the total merchant sales in 1942 compared with 2 percent in 1941, 3 percent in 1940, and 6 percent in 1937.

South Dakota sales of ground feldspar rose 14 percent in 1942 to 68,025 short tons (valued at \$483,075)—a record tonnage—giving it first place among the producing States. Tennessee ranked second, followed by Colorado, North Carolina, and New Hampshire. States that produced more ground spar than in 1941, in addition to South Dakota, with percentages of increase, were: Illinois, 0.5 percent; Arizona, 24; California, 37; and Virginia, 38 percent. The output from Tennessee and North Carolina combined decreased 10 percent compared with 1941. All other States reported declines in output of ground feldspar ranging from 12 percent for New Jersey and New York and 15 percent for Colorado to 29 percent for Maine and 34

percent for New Hampshire.

Ground feldspar sold by merchant mills 1 in the United States, 1938-42

	,	Domestic				Canadian	Total		
Year Active		Value			Value		-		
	milis	mills Short tons T	Total	Aver- age	Short	Total	Aver- age	Short tons	Value
1938 1939 1940 1941	30 31 29 29 29	206, 646 249, 889 277, 612 347, 092 318, 209	\$2, 314, 675 2, 685, 473 2, 912, 470 3, 646, 404 3, 339, 462	\$11. 20 10. 75 10. 49 10. 51 10. 49	7, 868 9, 305 8, 101 7, 325 9, 577	\$151, 577 176, 805 153, 012 136, 199 185, 507	\$19. 26 19. 00 18. 89 18. 59 19. 37	214, 514 259, 194 285, 713 354, 417 327, 786	\$2, 466, 252 2, 862, 278 3, 065, 482 3, 782, 603 3, 524, 969

<sup>1</sup> Excludes potters or others who grind for consumption in their own plants.

The downward trend in recent years in average realization for ground feldspar marketed in the United States was checked, at least temporarily, in 1942 when the average for all ground spar sold rose to \$10.75 per short ton compared with \$10.67 in 1941 and \$10.73 in 1940. The average value of ground spar sold was greater in all States except New Jersey, North Carolina, Tennessee, and Virginia. Percentages of increase in average realization ranged from 2 percent for New York and 10 percent for Arizona and California to 18 percent for New Hampshire. The range of average values for individual States in 1942 was \$6.75 to \$17.77, somewhat narrower than in 1941 when similar figures ranged from \$6.34 to \$17.92. Average realizations per ton for selected States in 1942 follow: Colorado, \$6.75; South Dakota. \$7.10; California, \$13.07; North Carolina-Tennessee, \$12.04; Maine, \$14.70; and New Jersey (including marketed spar ground in Connecticut), \$17.77.

According to Engineering and Mining Journal, Metal and Mineral Markets, quotations on ground feldspar during 1942 remained the same as in 1941. Potash spar in Maine and North Carolina, 200mesh, white, in bulk, was quoted at \$17 per short ton, f. o. b. mill; and soda spar, similarly prepared, at \$19. North Carolina granular glass spar, 20-mesh, white, in bulk, f. o. b. mill, brought \$12.50 per ton, with semigranular spar quoted at \$11.75. Virginia quotations, as listed in the same journal, were: No. 1, 230-mesh, \$18; 200-mesh, \$17; glassmakers' spar, No. 17, \$11.75, and No. 18, \$12.50. Enamelers' spar, either on Spruce Pine, N. C., or Keene, N. H., basis, was quoted at \$14 to \$16 per ton.

Ground feldspar sold by merchant mills 1 in the United States, 1940-42, by States

		1940			1941			1942	
State	Active mills	Short tons	Value	Active mills	Short tons	Value	Active mills	Short tons	Value
Arizona California Colorado. Connecticut. Illinois. Maine. New Hampshire. New Jersey. New York. North Carolina. Tennessee. South Dakota. Virginia. Undistributed 4.	1 3 3 1 1 1 3 2 3 4 4 3 2 2 2 1	(2) 2, 624 44, 260 (3) 19, 580 (2) 19, 580 (2) 3 21, 158 (2) 78, 077 54, 783 (2) 65, 231	(2) \$32, 847 282, 178 (3) 255, 020 (4) 3 379, 899 (7) 934, 702 374, 024 (8) 806, 812 3, 065, 482	1 3 3 1 1 1 3 2 3 4 4 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2	(2) 4,079 61,141 (3) (2) 19,713 (2) 25,672 (2) 95,391 59,581 (2) 88,840 354,417	(2) \$48, 292 387, 338 (3) 270, 434 (2) 3 459, 974 (2) 1, 179, 577 407, 454 (3) 1, 029, 534 3, 782, 603	1 3 3 1 1 1 3 2 3 4 4 2 2 2 2 2 2 2 2 2 2 2 2 2 2 2	(2) 5, 578 51, 684 (2) 14, 052 (2) 2, 22, 649 (2) 3, 22, 649 (2) 4, 68, 025 (2) 79, 558 327, 786	(2) \$72, 924 349, 065 (3) (2) 205, 633 (2) 205, 633 (2) 207, 479 (2) 1, 037, 998 483, 075 (2) 972, 795 3, 524, 969

Excludes potters or others who grind for consumption in their own plants.
 Included under "Undistributed."
 Connecticut included with New Jersey.
 Includes items indicated by "(2)."

#### CONSUMPTION AND USES

Crude feldspar.—Most crude feldspar is sold to merchant mills, which obtain their supply from a number of mines or localities. raw spar is stock-piled and sorted according to grade and source, then blended and ground to specified purity and fineness and sold to ultimate consumers. However, a few pottery and enamel manufacturers have purchased part or all of their feldspar requirements crude and

have ground it as needed in their own mills. Makers of soap, cleansers, and sweeping compounds also mine or purchase crude feldspar, largely from New England, Virginia, and North Carolina, and after grinding or otherwise processing it utilize the abrasive properties of the spar in their products. Manufacturers of artificial teeth annually use a small tonnage of carefully selected crude material, which must be free from all grit and is sold at a substantial premium over

No. 1 grade commercial feldspar.

Ground feldspar.—The ceramic industry uses well over 95 percent of the ground feldspar sold by merchant spar mills each year in the United States. Most of the spar, by far, is consumed in the glass, pottery, and enamel trades. The glass industry increased its share of feldspar used to 195,601 short tons or 60 percent of the total ground spar sold, compared with 52 percent in 1941. Sales of spar for use in pottery and in enamel fell sharply in 1942, each outlet having dropped approximately 20,000 tons from 1941; pottery decreased from 36 to 32 percent of the total marketed spar and enamel from 10 to 4 percent. The remainder of the ground feldspar sold by merchant mills was utilized for various ceramic uses other than glass, pottery, and enamel; for soaps and abrasive purposes; and for purposes not specified. Minor uses of feldspar include its employment as a welding-rod coating, and as a cementing material in laying firebrick walls.

Ground feldspar sold by merchant mills in the United States, 1940-42, by uses

	19	40	19	41	1942		
Use 7	Short tons	Percent of total	Short tons	Percent of total	Short tons	Percent of total	
Ceramic: Glass. Pottery. Enamel Other ceramic uses. Soaps and abrasives. Other uses.	149, 623 104, 586 26, 420 649 2, 682 1, 753	52. 4 36. 6 9. 3 . 2 . 9	182, 878 127, 140 34, 841 563 1, 490 7, 505	51. 6 35. 9 9. 8 . 2 . 4 2. 1	195, 601 106, 081 13, 899 6, 459 4, 396 1, 350	59. 7 32. 4 4. 2 2. 0 1. 3	
	285, 713	100.0	354, 417	100.0	327, 786	100.0	

The destinations of ground feldspar from 1939 to 1942, as reported by merchant grinders, are shown in the accompanying table. Shipments during 1942 to California, Illinois, and West Virginia increased considerably over 1941 but to New York only slightly. Other States for which comparisons are possible showed smaller totals than in 1941, although generally quantities compared favorably with those for prior years. In 1942 the largest consuming State was Illinois, with shipments amounting to 50,450 short tons or 15 percent of the total; it was followed by Ohio with 43,950 tons (13 percent), New Jersey with 43,029 tons (13 percent), Pennsylvania with 40,013 tons (12 percent), and Indiana with 38,998 tons (12 percent). Next in order were West Virginia (11 percent), New York (6 percent), and California (4 percent). Shipments to "Other destinations" comprised 4 percent of the total in 1942, including fair-size tonnages to Arkansas, Louisiana, Mississippi, and Texas and small amounts to some 15 or 20 other States.

<sup>1</sup> See Ralston, Oliver C., and von Bernewitz, M. W., Minerals Used in Welding: Bureau of Mines Inf. Circ. 7121, 1940, 56 pp.

Ground feldspar shipped from merchant mills in the United States, 1939-42, by destinations, in short tons

Destination	1939 1	1940	1941	1942
California Illinois Indiana Maryland Massachusetts New Jersey New York Ohio Oklahoma Pennsylvania Tennessee West Virginia Wisconsin Other destinations 3	7, 590 15, 948 38, 189 (2) (2) 34, 309 14, 995 53, 410 (2) 37, 466 5, 077 19, 188 5, 134 25, 463	7, 897 32, 811 28, 634 (2) (2) 42, 381 13, 236 50, 835 (2) 47, 431 5, 911 21, 839 6, 967 27, 721	10, 444 44, 573 39, 620 (*) 44, 249 18, 326 52, 270 (*) 54, 534 9, 697 29, 916 10, 517 40, 271	12, 222 50, 456 38, 908 8, 744 3, 636 43, 925 8, 905 40, 012 3, 505 35, 163 7, 837 13, 877

# NEPHELINE SYENITE

Production of nepheline syenite in 1942 continued active. first years it was used, practically all was employed in the manufacture of glass where its high alumina content proves economical and benefi-In more recent years an increasing proportion of the output has gone into various types of ceramic bodies. The glass-trade material is of granular type, whereas nepheline for pottery use is finely ground. A residue or dust remaining from grinding finds an outlet partly in the enamel and colored-glass trades and partly as a substitute for pumice for grinding and polishing, as a cleanser, and in the heavy-clay industries.

Production in the last 2 or 3 years has come almost entirely from the Methuen Township region in Peterborough County, Ontario. Deposits of similar occurrence extend over into Hastings and Hali-The Bancroft-Gooderham district northeast of the burton Counties. Methuen region in Hastings and Haliburton Counties has produced intermittently since 1937. A new Canadian source of nepheline syenite is the property of Port Coldwell Mines & Metals, Ltd., recently reported to be under development<sup>2</sup> at Port Coldwell, Ontario.

The larger part of the Canadian output is shipped into the United States for grinding and consumption, although some nepheline is ground before importation. After considerable increase in 1941 over 1939 and 1940, imports of crude nepheline syenite in 1942, although only slightly above 1941, reached the record figure of 35,990 short tons Comparable data are 35,799 tons valued at valued at \$120,688. \$112,101 in 1941 and 27,888 tons valued at \$87,162 in 1940. Ground nepheline syenite imported into the United States totaled 4 short tons valued at \$44 in 1942, which compares with 6 tons valued at \$25 in 1940; in 1941, however, 1,359 short tons of ground nepheline valued at \$13,695 were shipped into this country. All shipments of crude and ground nepheline originated in Canada.

Prices of nepheline syenite at the end of 1942, according to Canadian

<sup>&</sup>lt;sup>1</sup> Data include 99 percent of total ground feldspar.

<sup>2</sup> Included under "Other destinations"; separate figure for State not available.

<sup>3</sup> Includes Arkansas, Colorado, District of Columbia, Hawaii, Kentucky, Louisiana, Maryland (1939-41), Massachusetts (1939-41), Michigan, Minnesota, Missispi, Missouri, Oklahoma (1939-41), Puerto Rico, South Carolina, and Texas, and other States (shipments to which cannot be segregated); also small shipments to Canada, England, and Mexico.

<sup>&</sup>lt;sup>2</sup> Northern Miner, vol. 28, No. 46, February 4, 1943, p. 8.

Chemistry and Process Industries, were the same as at the beginning of the year: Grade A, 20-mesh, bulk, in carlots, \$11.75 per ton f. o. b. Lakefield, Ontario; Grade A, 200-mesh, bulk, in carlots, \$16.50 per ton f. o. b. Kingston, Ontario; and Grade B dust, bulk, in carlots, \$10.00 per ton, f. o. b. Lakefield, Ontario.

Nepheline syenite prices were included under the Office of Price Administration General Maximum Price Regulation (G. M. P. R.) of April 28, 1942, and also under Maximum Price Regulation

(M. P. R.) 327, issued February 16, 1943, and effective February 22, 1943. This latter regulation established as the maximum allowable prices those prevailing in March 1942.

The only known commercial production of nepheline syenite, other than from Canadian deposits, is that from apatite nephelite rock on the Kola Peninsula in northwestern U. S. S. R. Montana pegmatites, said to resemble in part the Kola Peninsula deposits, were described by Pecora.3

## APLITE

Production of ground "aplite" by Dominion Minerals, Inc., with mill at Piney River, Va., continued at an active rate in 1942, surpassing slightly shipments reported for 1941. New uses, especially for the large quantities of fines produced as a byproduct of milling operations, are being investigated. Among possible new uses may be fillers of various types and a quite recent application—the extinguishing of incendiary magnesium bombs.

The new mill of the Carolina Mineral Co., Erwin, Tenn., subsidiary of the Consolidated Feldspar Corporation, began operations during 1942, grinding material similar to that processed by Dominion Minerals, Inc. The new plant also is located near Piney River, Va.

## TECHNOLOGIC DEVELOPMENTS

Considerable data on the fluxing properties of feldspar and nepheline syenite were developed and published in a paper by Earhart.4 In a study of the effect of fluxes containing mixtures of spodumene and feldspar on semivitreous and vitreous hotel-chinaware bodies, the most effective fluxes were found to be those consisting of 30 to 40 percent spodumene, 40 to 60 percent potash feldspar, and 10 to 20 percent soda feldspar. Formulas for determining the relative amounts of microcline, albite, anorthite, kaolinite, muscovite, and free quartz in the feldspars were published by Koenig.6 The extent and nature of feldspar-bearing sands in Illinois and the most economical methods of separating and preparing commercial grades of feldspar from them were investigated by the State Geological Survey during 1942.7

Feldspar has been found to be effective in extinguishing magnesium

<sup>&</sup>lt;sup>3</sup> Pecora, William T., Nepheline Syenite Pegmatites, Rocky Boy Stock, Bearpaw Mountains, Montana: Am. Mineral., vol. 27, No. 6, June 1942, pp. 398-424:

<sup>4</sup> Earhart, William H., Use of Washed North Carolina Kaolin as an Ingredient of Porcelain Bodies: Ohio State Univ. Studies, Eng. Exp. Sta. Circ. 42, November 1941, 40 pp. Schurecht, H. G., Shapiro, J. K., and Zabawsky, Z., Influence of Fluxes of Spodumene and Feldspar Mixtures on Properties of Chinaware Bodies: Jour. Am. Ceram. Soc., vol. 25, No. 11, July 1, 1942, pp. 321, 396

<sup>321-326.

§</sup> Ko enig, E. W., Calculation of Mineralogical Composition of Feldspar by Chemical Analysis: Jour. Am. Ceram. Soc., vol. 25, No. 14, October 1, 1942, pp. 420-422.

§ Willman, H. B., Feldspar in Illinois Sands: Illinois State Geol. Survey, Rept. of Investigations 79. Urbana, Ill., 1942, 87 pp.

incendiary bombs,8 as a result of experiments by W. W. Rubey geologist, and Michael Fleischer and J. J. Fahey, chemists, Federal Geological Survey. With a melting point of about 2100° F.—lower than that of sand-feldspar quickly forms a protective coating over the molten magnesium which cuts off the supply of air from the magnesium and actually stops it from burning and its flame from spreading. It is superior to mixtures containing salt, pitch, ashes, or fine powders, as it does not burn, give off smoke, blow out, or scatter appreciably from the intense heat of the incendiary material. Feldspar used for this purpose should be ground to pass a 10-mesh screen and be retained by a 200-mesh screen. Finer material tends to clog interstices and prevent the ready escape of gases, which otherwise would erupt with sufficient force to form miniature craters in the feldspar cover and destroy its effectiveness.

Costly equipment or a trained crew is not needed to apply the extinguisher. Feldspar also is relatively inexpensive. Indeed, the waste material produced in grinding commercial grades of spar could readily be screened to suitable size and marketed for this purpose at

comparatively low cost, according to the Geological Survey.

In most of the Survey experiments, the rock used consisted largely of soda-lime feldspar: This rock, locally called "aplite," is quarried in Amherst and Nelson Counties, Va., where there is an abundant supply. Potash feldspar, either orthoclase or microcline, is equally effective. Rocks consisting largely of feldspar also give practically as good results as pure feldspar. In the East such materials as syenites, nepheline syenites, or screenings from granite quarrying might be used. Granite, monzonite, rhyolite, and latite are available and quarried for crushed stone in the Pacific Coast area. Screenings from these crushed rocks, although perhaps not as effective as feld-

spar, could be utilized as magnesium extinguishers.

The United States Department of the Interior, by arrangement with the inventors acting through the Department of Justice, already has taken steps to obtain Government-controlled patent protection for the invention and method of use. Under the patent, commercial development of the material under free licenses will be encouraged by the Department. Consumer prices for material used in extinguishing incendiary magnesium to be sold under the above-noted patent, were established by the Office of Price Administration.<sup>10</sup> Up to February 1943, sales of extinguishers manufactured by license had been made in Baltimore and Philadelphia. Applications for licenses also had been received from potential manufacturers elsewhere in the East, on the West coast, and in the Gulf of Mexico area. Interest in the extinguisher has been shown by airfields and by factories using magnesium in their products.

#### OTHER DEVELOPMENTS

The property of the Seaboard Feldspar Corporation in Cheshire County, N. H., was acquired in July 1942 by the General Minerals Corporation, 52 William Street, New York City, and operation con-

Bepartment of the Interior Information Service, Press Release, June 14, 1942, 3 pp.
 Fahey, Joseph J., Fleischer, Michael, and Rubey, William W. (assigned to U. S. Government), Method and Means for Extinguishing Burning Molten Magnesium and the Like: U. S. Patent 2,294,532, September 1, 1942.
 Office of Price Administration, Feldspar Fire Extinguishers: OPA Maximum Price Regulation 321 (effective February 24, 1943), reported in OPA Press Release, February 19, 1943.

tinued during the year. In August 1942, the F. E. Schundler Feldspar Co., Inc., Custer, S. Dak., discontinued business, and the company was dissolved. The Consolidated Feldspar Corporation, Trenton. N. J., also operating a mill at Keystone, S. Dak., acquired the mines and mill of the Schundler firm and operated the plant for the rest of the year. The Bureau of Mines has been informed that a feldspar mill is to be erected in the Llano area at Kingsland, Tex., to process a low-iron spar recently discovered in the Packsaddle

Mountain district.

Brief descriptions of feldspar deposits are given and the relative importance of the New York feldspar industry is discussed by Otte.11 The feldspar occurrences in the Llano County region in Texas were described by Chelf. 12 Two plants of the Consolidated Feldspar Corporation, whose main offices are in Trenton, N. J., were described in the trade press. Hubbell 13 presented a detailed account of the equipment, products, and methods of operation of the corporation plant at Erwin, Tenn., which processes feldspar from the Spruce Pine area of North Carolina; and Moore 14 described operation of the mines and mill near Bedford, Westchester County, N. Y.

## IMPORTS 15

Feldspar.—Crude feldspar imported into the United States in 1942 aggregated 9,525 long tons valued at \$69,797—a decrease of 15 percent in tonnage and 5 percent in value compared with 11,253 tons valued at \$73,236 imported in 1941; the average value per ton (\$6.51 in 1941) increased 13 percent to \$7.33 in 1942. All imports originated in Canada. In 1942, as in 1940 and 1941, there were no imports of ground feldspar.

Feldspar imported for consumption in the United States, 1938-42

	Cm	nde Gro		und		Cr	ade	Gro	und
Year	Long tons	Value	Short tons	Value	Year	Long tons	Value	Short tons	Value
1938 1939 1940	7, 651 7, 460 12, 522	\$56, 126 52, 141 80, 274	2	\$54	1941 1942	11, 253 9, 525	\$73, 236 69, 797		

Cornwall stone.—Both "unmanufactured" and "crushed or ground" Cornwall stone from the United Kingdom (only source of supply for this material) were actively imported into the United States during 1941; in 1942, however, shipments virtually ceased. The average values (foreign market value) per long ton for unmanufactured material in 1940, 1941, and 1942 were, respectively, \$9.20, \$11.38, and \$13.80 and for crushed or ground Cornwall stone, \$12.10, \$14.60, and \$18.40.

52-53.

Beginning the Bureau of Mines, from records of the Department is Figures on imports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce,

<sup>11</sup> Otte, Herman F., The Expanding Mineral Industry of the Adirondacks: State of New York, Executive Department, Division of Commerce, Pub. 10, Albany, N.Y., February 1943, 102 pp. (Feldspar, pp. 89-95.)

12 Chelf, Carl, A New Feldspar Deposit in Llano County, Tex.: Univ. of Texas, Bureau of Economic Geology, Mineral Resources Survey Circ. 45, May 1942, 5, pp.

13 Hubbell, A. H., A Feldspar Grinding Plant in Tennessee: Eng. and Min. Jour., vol. 143, No. 12, December 1942, pp. 67-68.

14 Moore, R. Carl, Mining and Grinding Feldspar: Rock Products, vol. 45, No. 9, September 1942, pp.

# Cornwall stone imported for consumption in the United States, 1938-42

	Unmanufactured		Ground			Unmanufactured		Ground	
Year	Long tons	Value	Long tons	Value	Year	Long tons	Value	Long tons	Value
1938 1939 1940	513 1,684 2,261	\$4, 976 17, 233 20, 812	233 348 228	\$1,797 3,965 2,758	1941 1942	2, 736 74	\$31, 138 1, 021	182 5	\$2, 658 92

## WORLD PRODUCTION

World output of feldspar from 1937 to 1942, insofar as data are available, appears in the following table.

World production of feldspar, 1937-42, by countries, in metric tons 1 [Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
	1 940	620	1 051	1, 220	9 001	(9)
Argentina (shipments) Australia:	1, 346	620	1,051	1, 220	2, 981	(2)
New South Wales/3	162	178	(2)	(2)	(2)	(2)
South Australia 3	669	502	615	1,072	1,081	(3)
Western Australia (ex-	0.001	0.010	0.050	0.505	<b>(e)</b>	(0)
ports) Brazil	3, 031 8, 400	2, 919 (2)	3, 853 (2)	3, 561 (2)	(2)	(2)
Canada (shipments)	19, 365	12,753	11,306	19, 464	23, 623	21, 24
Egypt	158	199	74	138	52	(3)
Finland (exports)	3, 232	5,046	5, 596	(2)	(2)	(2)
France	8, 900	(2)	(2)	(2)	(2)	(2)
Jermany: Bavaria India, British	9, 986 495	10, 419 702	501		(2)	(2)
taly	13, 437	13, 391	(2)	2	(2)	(2)
Norway (exports)	32, 555	21, 761	21, 282	(2)	(2)	(2)
Rumania	2, 587	1,690	(2)	(2)	(2)	(2)
Sweden United States (sold or used)	49, 140 272, 842	45, 111 199, 267	40, 792 257, 534	(2) 295, 430	344, 299	312, 76

In addition to countries listed, feldspar is produced in China (Manchuria) and Czechoslovakia. Official figures of Czechoslovak output are not available, but it is estimated that the annual production is approximately 30,000 metric tons (Stat. Comm. Czechoslovak Ceram, Soc.).
 Pata not available.
 Includes some china stone.

# **ASBESTOS**

By OLIVER BOWLES AND F. M. BARSIGIAN

#### SUMMARY OUTLINE

	Page		Page
Acceptable to the control of the con		New developments	1428
Summary Salient statistics	1425	Foreign trade	1429
Domestic industry	1425	World production	1430
Review by States	1425	Canada	1431 1431
Trends in consumption	1426	Africa	1432
Market conditions	1427	Soviet Russia	1433
Dwices	1428	Other countries	_100

# SUMMARY

Sales of domestic asbestos in 1942—15,481 short tons—were 37 percent less than those in 1941. The decline was confined to the chrysotile variety, sales of which were smaller both in Vermont and Arizona. The value of total sales was 31 percent lower. Sales of the amphibole variety were slightly higher in both quantity and value than in 1941. Most of the United States production is of the shorter grades of chrysotile. During 1942 domestic production furnished less than 4 percent of domestic requirements.

As in the past, Canada supplied most of the United States needs of unmanufactured asbestos. Canadian chrysotile is of excellent quality and is suitable for most asbestos products, although a few specialties require asbestos from other sources. African chrysotile, which is imported in substantial quantities, is an important supplement to Canadian fibers of spinning grade. India and Soviet Russia are other

sources of chrysotile for general use.

Asbestos combines noninflammability with a fibrous structure that makes it the unique source of unburnable fabrics. Because of this peculiar combination of properties it is an irreplaceable material for certain important military uses, although for some common uses substitution is possible. The most important application in the former category is for brake linings and clutch facings on automobile transport equipment. No satisfactory substitute has been found for these uses. As all types of automotive transport must have brakes and clutch facings, it is apparent that the military needs are extensive and of primary importance. Fortunately, any strong, flexible chrysotile of spinnable length is satisfactory for such use, and the extensive asbestos-producing industry of Canada can supply large quantities of satisfactory material. The demands for spinning fibers in this field are relieved to some extent by the substitution of molded for woven brake bands. The molded bands employ shorter grades of fiber, but they can be used only on certain types of brakes. Other important asbestos products are gaskets and packings around steam and com-

pressed-air machinery. These products are also of great military importance because they are used on warships, by the merchant marine, and in even larger quantities at power plants and innumerable munition factories.

Still another important field of usefulness for asbestos is heat insulation. Asbestos is a popular insulating medium; but other materials are substituted for it to some extent, and further substitution in the general insulation field is possible. There are, however, certain types of insulation for which special grades of asbestos are essential if weight

is to be conserved and efficiency maintained.

The most widespread occurrences of asbestos in the United States are those of the amphibole type—anthophyllite and tremolite. Hundreds of deposits are known, but production never exceeds a few hundred tons a year because the uses are quite limited. Its resistance to acids renders tremolite useful for making chemical filters; the amphibole varieties are employed also in arc welding and in making insulation products, but the uses are so restricted and relatively so unimportant that they are not classed as critical.

Chrysotile asbestos is the principal variety of commerce and occupies an important place in the war program. The principal world production centers are Quebec (Canada), Rhodesia, Union of South Africa, Swaziland, and Soviet Russia. The Canadian mines and mills supply most of the United States needs, and the quality of the product is satisfactory for most of the important uses. African chrysotile is superior for electric-insulation products that must be low in iron and therefore

is regarded as essential to the military program.

Amosite, a variety of asbestos mined only in Africa, consists of long, strong fibers that are superior for making lightweight insulation to be used around steam machinery on warships. Amosite also is preferred for making 85-percent magnesia pipe covering and a block insulation of similar type that contains no magnesia. This variety is therefore regarded as essential to the highest naval efficiency. In June 1942 the War Production Board promulgated Conservation Order M-79 restricting the use of amosite in 85-percent magnesia to certain military applications.

Crocidolite or blue asbestos is regarded as essential because it is superior to other varieties in making asbestos-cement pressure pipes, chemical filters, and acid-resistant packings. Long blue fiber is used also in making gas masks. Blue asbestos is mined chiefly in Africa,

but small quantities are obtained in Australia.

Beginning January 1943, fiber obtainable from the two leading producing companies in Africa was purchased on United States Government account by the Metals Reserve Co. and allocated to the various asbestos-products manufacturers. This plan offered certain advantages in control of shipping routes, stimulation of production, and allocation according to the most urgent needs.

Throughout 1942 the Bureau of Mines conducted a monthly canvass for the War Production Board, covering receipts, stocks, and consumption. Stocks of critical grades of African fibers in the hands of consumers at the end of 1942 were adequate for 6 to 8 months' use

at the average rate of consumption during the year.

Salient statistics on asbestos for 1941 and 1942 are summarized in the following table.

Salient statistics of the asbestos industry in the United States, 1941-42

	19	41	1942		
	Short tons	Value	Short tons	Value	
Domestic asbestos— Produced:					
Chrysotile Amphibole	20, 144 2, 252	(1)	13, 109 2, 208	(1)	
Total produced	22, 396	(1)	15, 317	(1)	
Sold or used by producers: Chrysotile Amphibole	22, 439 1, 952	\$707, 589 18, 164	13, 373 2, 108	\$480, 245 18, 612	
Total sold or used by producers	24, 391 419, 196 4, 846 3 438, 741 (1)	725, 753 17, 909, 077 325, 825 3 18, 309, 005 4, 835, 194	15, 481 419, 414 774 434, 121	498, 857 21, 235, 266 134, 083 21, 600, 040 5, 114, 496	

Figures not available.
 Quantity sold or used by producers, plus imports, minus exports.
 Revised figures.

The following table shows domestic production of asbestos during recent years according to varieties.

Asbestos sold or used by producers in the United States, 1938-42, by varieties

	Chry	sotile	Amp	hibole	Total		
Year  1938	(1) 15, 043 18, 672 22, 439 13, 373	(1) \$503, 097 664, 520 707, 589 480, 245	(1) 416 1,388 1,952 2,108	(1) \$9, 691 9, 988 18, 164 18, 612	10, 440 15, 459 20, 060 24, 391 15, 481	Value \$247, 264 512, 788 674, 508 725, 753 498, 857	

<sup>1</sup> Bureau of Mines not at liberty to publish figures separately for chrysotile and amphibole.

#### DOMESTIC INDUSTRY

#### REVIEW BY STATES

Arizona.—Production of asbestos in Arizona was less than half as great in 1942 as in 1941, according to reports of producers submitted to the Bureau of Mines. Sales, which were about two-thirds those in 1941, were made by the following companies: Arizona Chrysotile Asbestos Co., Arthur Enders, Guy G. Phillips, and Pine Top Asbestos Mines, all of Globe, Ariz.; E. E. Prochnow, Winslow, Ariz.; Fiber & Metal Products Co., Downey, Calif.; Gladding, McBean & Co., 2901 Los Feliz Boulevard, Los Angeles, Calif.; and Johns-Manville Products Comparation 20 Fast Fortisth Street New York N. V. Products Corporation, 22 East Fortieth Street, New York, N. Y.

The Johns-Manville Products Corporation completed its new mill at Chrysotile, Ariz., but the output in 1942 was quite limited. it attains normal operation the mill will afford a means of grading and classifying Arizona asbestos more accurately than has been pos-

sible in the past.

Pine Top Asbestos Mines began development of a property in the San Carlos Indian Reservation in May 1942, and shipments of fiber were made later in the year. Plans are under way for systematic development of the property and for erection of a mill.

California.—Kohler & Chase, 26 O'Farrell St., San Francisco, produced short-fiber chrysotile from its property near Monticello, Napa County. This was the only asbestos-mining activity noted in

California during 1942.

Georgia.—The only activity reported from Georgia was that of the Powhatan Mining Co., which continued operation of its amphibole

asbestos property near Dillard, Rabun County.

North Carolina.—Sales of North Carolina amphibole asbestos, only variety mined in the State, were 20 percent greater in 1942 than in W. T. Hippey and the Powhatan Mining Co. continued to operate their mines in the Micaville area of Yancey County. Industrial Minerals Corporation (Asheville) began production from a new property near Newdale, Yancey County, early in 1942 and marketed substantial quantities before the end of the year. According to report, the asbestos-bearing rock mass is at least 200 feet wide and 400 feet long. It gives promise of production on a larger scale than is possible at most amphibole deposits.

Oregon.—A small quantity of tremolite asbestos was produced from a property owned by Mrs. Flora Winsenberg (Azalea, Oreg.)

near Rogue River, Jackson County.

Vermont.—The Vermont Asbestos Mines Division of the Ruberoid Co. (500 Fifth Ave., New York, N. Y.), largest producer of asbestos in the United States, continued to operate its open-pit mine and well-equipped mill near Eden, Lamoille County. Shingle stock and molded brake-lining fiber are important products, but several shorter grades are produced in large quantities. The volume of output was somewhat lower than in 1941.

## TRENDS IN CONSUMPTION

Trends in the asbestos-products industries during recent years are indicated in the following table.

Raw asbestos consumed in the United States and asbestos products manufactured in and exported from the United States, 1937-42

-	Raw as- bestos—	Asbestos products—			Raw as- bestos—	Asbestos products—		
Year	apparent consump- tion (short tons)	Manufac- tured <sup>1</sup>	Exported 2	Year	apparent consump- tion (short tons)	Manufac- tured <sup>1</sup>	Exported 2	
1937	316, 263 187, 150 255, 547	\$96, 347, 570 (1) 97, 944, 735	\$3, 047, 078 2, 533, 916 3, 354, 920	1940 1941 1942	262, 199 3 438, 741 434, 121	(1) (4) (1)	\$3, 473, 248 4, 835, 194 5, 114, 496	

Figures of Bureau of the Census (collected biennially for odd years) include value of certain gaskets, packing, and similar products in which little asbestos was employed.
 Compiled from records of the Department of Commerce.
 Revised figures.

4 Data not available.

Under normal conditions the consumption of asbestos is governed to quite an extent by the number of automobiles manufactured, be-

cause all kinds of automotive transport equipment require asbestos brake bands and clutch facings. During 1942 the manufacture of automobiles was virtually suspended and therefore ceased to be a market indicator. Activity in building construction also influences asbestos sales, because asbestos heat-insulation and fireproofing materials as well as asbestos-cement building materials (such as shingles, siding, and wallboard) are used extensively. Private building declined greatly in 1942, but military construction (including defense housing) was very active and was responsible for large sales of asbestos products. Industrial activity, which maintained a very high level, involved extensive power-plant construction. Large quantities of packings, gaskets, boiler lagging, and pipe covering were consumed in these plants and in multitudes of munition factories. Asbestos is an essential raw material for ship construction, and the rapid expansion of the Navy and Merchant Marine accounted for a large proportion of the sales of high-grade fibers during 1942. ure 1 shows the relationship of asbestos consumption to building construction and industrial activity for a period of years. It is evident that asbestos consumption is related more closely to industrial activity than to building construction.




FIGURE 1.—Consumption of asbestos compared with total new construction and industrial production, 1920-42. Units are reduced to percentages of the 1935-39 average. Statistics on the value of construction from the Bureau of Foreign and Domestic Commerce and on industrial production from the Federal Reserve Board.

#### MARKET CONDITIONS

Over-all market demands for asbestos, which surpassed in 1941 all previous records, declined slightly in 1942. Needs in the automobile industry were confined largely to replacements, but loss of market in this field was compensated by the growing demands of the war program. Civilian uses of the more critical grades were restricted to insure adequate supplies for war needs. The demand for spinning fibers was very strong and threatened to outstrip the supply during the latter part of the year.

#### PRICES

Prices for asbestos are quoted upon a short-ton basis from Metal and Mineral Markets, published by the McGraw-Hill Publishing Co., Inc., New York City. Canadian prices are f. o. b. Quebec mines, tax and bags included; Vermont prices are f. o. b. mines,

Hyde Park, Vt.
Prices of all Canadian fibers remained at the levels of 1941, as quoted in Minerals Yearbook for that year, until April 1942, when all grades except Crude No. 1 were advanced as follows and remained constant thereafter: Crude No. 1, \$650-\$750; Crude No. 2 and sundry crudes, \$165-\$385; spinning fibers, \$124-\$233; magnesia, and compressed sheet fibers, \$124-\$146.50; shingle stock, \$62.50-\$85; paper stock, \$44-\$49; cement stock, \$28.50-\$33; floats, \$19.50-\$21; and shorts, \$14.50-\$26.50. Canadian prices are in United States dollars.

African and Russian fibers were not quoted during 1942.

In April 1942 prices of all grades of Vermont fibers were advanced substantially from 1941 figures. Quotations from April to the end of the year were as follows: Shingle stock, \$62.50-\$65.50; paper stock, \$44-\$53; waste, \$33; shorts, \$14.50-\$28.50; and floats, \$19.50.

# NEW DEVELOPMENTS

A new type of block insulation has been developed for uses similar to those of 85-percent magnesia. It consists of amosite asbestos with a binder but contains no magnesia—an advantage under present conditions, when there is an abnormally high demand for magnesia to be used in making refractories and metallic magnesium. The new product compares favorably with 85-percent magnesia in thermal conductivity, shrinkage, and strength.

Venezuela's new asbestos mill near Tinaquillo was under construction in 1942 but owing to difficulties in securing equipment was not

completed.

Blue asbestos is now mined in a small way in the Hammersley Ranges of Western Australia. Hand-cobbed fiber is of excellent quality, commanding about \$300 a ton at American ports. Supplies from this source are not great because the deposits are in very rough country

where transportation facilities are inadequate.

It is reported that Germany is obtaining small quantities of asbestos in Norway. The small pre-war output of Finland, Italy, and Czechoslovakia would be entirely inadequate for German war needs. data are available on the increased output from the small known sources of asbestos in Central Europe or the extent of reserve stocks held by Germany, and only meager information is at hand on substitute materials.

An asbestos-graphite lightweight molded product has been developed recently and sold under the trade name "seybolite." It is highly resistant to moisture, acids, alkalies, and fire. Suggested uses include molded seamless conduits, chemical containers, and fireproof panels

for ships, trucks, and airplanes.

A new lightweight asbestos fabric sold under the trade name "asbeston" is taking the place of critical metals in aircraft fittings, such as carburetor-intake attachments, heater-hose nozzles, and defrosters.

# FOREIGN TRADE 1

The following table shows imports of unmanufactured asbestos into the United States in 1941 and 1942. The volume of imports in 1942 was virtually unchanged from 1941. Imports from Africa were only slightly lower than in 1941 even though ship sinkings caused several serious losses. As most of the African fibers are of strategic grades, it is highly desirable to maintain imports at undiminished levels. Canadian imports fell a little below those of 1941, but the value of imports was more than 3 million dollars higher, due chiefly to advance in prices; larger purchases of the better grades of fibers probably accounted for some of the increase.

Asbestos (unmanufactured) imported for consumption in the United States, 1941-42, by countries and classes

	Crude (including blue fiber)		Mill fibers		Short fibers 1		Total	
Country	Short	Value	Short tons	Value	Short tons	Value	Short tons	Value
1941 Africa: 1941 Union of South Africa "Other British" Australia Bolivia	21, 447 8, 234 62 22				4	\$142	8, 234 62 22	
Canada India, British United Kingdom	3, 362 35 1			\$9, 401, 893	222, 398		389, 391 35 1	14, 531, 943 12, 646 510
1942 Africa:	33, 163	4, 266, 283	163, 631	9, 401, 893	222, 402	4, 240, 901	419, 196	17, 909, 077
Union of South Africa "Other British" Australia Bolivia Canada	20, 424 8, 665 35 16 2, 959	1, 386, 782 6, 879 2, 093		11, 407, 510	218, 600	5. 063. 349	20, 424 8, 665 35 16 386, 647	
India and Dependencies (British India) U. S. S. R.	17 673	9, 255 56, 552	2, 937	215, 925			3, 610	9, 255 272, 477
	32, 789	4, 548, 482	168, 025	11, 623, 435	218, 600	5, 063, 349	419, 414	21, 235, 266

<sup>1</sup> Asbestos, n. e. s., containing not over 15 percent foreign matter.

The following table shows imports and exports of unmanufactured asbestos for the 5-year period 1938-42.

Asbestos (unmanafactured) imported for consumption in and exported from the United States, 1938-42

Year	Imp	orts	Exports		
	Short tons	Value	Short tons	Value	
1938	179, 490 242, 561 246, 613 419, 196 419, 414	\$6, 160, 602 9, 094, 538 10, 034, 433 17, 909, 077 21, 235, 266	2, 780 2, 473 4, 474 4, 846 774	3 218,830 4 449,10	

 $<sup>^1\</sup>mathrm{Figures}$  on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

The following table shows exports of asbestos products in 1941 and 1942.

Manufactured asbestos products exported from the United States, 1941-42, by kinds

		1941	1942		
Product	Quantity	Value	Quantity	Value	
Brake lining:				and Haryan	
Molded and semimolded short tons	(1)	\$1, 150, 386	1,810	\$1, 706, 624	
Not molded linear feet	1, 277, 562	285, 192	749, 449	283, 900	
Clutch facing number	1,006,371	364, 420	1, 431, 512	558, 190	
Paper, millboard, and roll boardshort tons	1,540	212, 157	679	102, 660	
Pipe covering and cementdo	1, 187	136, 501	1,063	135, 158	
Textiles, yarn, and packingdo	1, 556	1, 356, 793	1,017	1, 154, 241	
Asbestos roofingsquares	82, 149	334, 246	97,668	169, 331	
Other asbestos manufactures, except roofing					
short tons	4, 431	679, 466	3,000	778, 547	
Magnesia and manufacturesdo	2, 155	316, 033	1,305	225, 845	
		4, 835, 194		5, 114, 496	

<sup>1</sup> Quantity not recorded.

# WORLD PRODUCTION

The following table shows production of asbestos throughout the world, by countries, from 1937 to 1942, insofar as figures are available.

World production of asbestos, 1937-42, by countries, in metric tons 1 [Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
Argentina			110	150	84	(2)
Australia: South Australia						
		49	46	119	152	(2)
Tasmania		100		364	(2) (2)	(2)
Western Australia		123	279 3 2	304 3 71	<sup>3</sup> 211	(2) 3 58
Bolivia Brazil		21 120	45	500	8 13	(2)
Canada 4		262, 894	330, 642	313, 504	433, 492	398, 669
	(2)			100	(2)	(2)
ChinaChosen	70	(2)	(2) (2)	(2)	(2)	(2)
Cyprus (exports)	11, 892	5, 668	9, 970	9, 652	(2)	(2)
Finland 5	7, 260	(2)	(2)	(2)	(2)	(2)
France		(2) (2)	(2) (2)	(2)	(2)	(2)
Greece	2	85		(2)	(2)	(2)
India, British		90	266	61	6.32	6 18
Indochina			(2)	(2) (2)	(2)	(2)
[taly		6,860	(2)	(2)	(2)	(2)
Japan (approximate)		1,000	1,000	1,000	(2) (2) (2) (2)	(2)
Kenya Colony		5	(2) (2)	(2)		(2)
New Zealand	(2)	(2)		7 22. 127	54	
Southern RhodesiaSwaziland	51, 722	53, 352	52, 900 7, 233	18, 873	(2)	(2) (2)
Turkev		668	1, 200 88	(2)	(2) (2)	(2)
Uganda		53	(2)	(2)	(2)	(2)
Union of South Africa		21, 025	20, 003	24 849	8 25, 400	8 31, 000
U. S. S. R.	125,000	86,000	(2)	(2)	(2)	(2)
United States (sold or used by producers).		9, 471	14,024	18, 198	22, 127	14,04
Venezuela.	(2)	(2)	(2)	20, 20	(2)	(2)

<sup>&</sup>lt;sup>1</sup> In addition to countries listed, asbestos is produced in Bulgaria, Czechoślovakia, and Madagascar.

Data not available.

<sup>Exports.
Exports.
Exclusive of sand, gravel, and stone (waste rock only), production of which is reported as follows: 1937, 3,611 tons; 1938, 2,975 tons; 1939, 3,535 tons; 1940-42, data not available.
Includes asbestos flour.</sup> 

<sup>6</sup> Imports into United States, 7 January to May, inclusive. 8 Preliminary.

#### CANADA

Canadian mines and mills were operating virtually at capacity during 1942. Supplies of mill fibers were ample for United States requirements, but a possible shortage of No. 2 crude was threatened during the latter part of the year. It is claimed that the percentage of crude fibers recovered in the Quebec mines is declining, and the cause of the decline is attributed to the method of mining. Several of the larger mines now employ the block-caving method, which involves undermining great masses of asbestos-bearing rock and removing the broken stone from tunnels underneath the rock mass. The block of stone is shattered under the stress of forces set up as it settles unevenly; and as the fiber veins are planes of weakness, shatter cracks tend to follow the veins, breaking them up in such a manner that much of the fiberformerly hand-cobbed as crudes—is mixed with the rock and recovered later as mill fiber. The United States is so dependent on Canada for its high-grade fibers that all such trends must be followed closely.

The following figures have been released by the Department of

Mines, Province of Quebec, for strictly confidential use.

Sales of asbestos in Canada, 1941-42, by grades

		1941		1942			
	Short	Va	lue	Short tons	Value		
	tons	Total	Average per ton		Total	Average per ton	
Grade: Crudes Fibers Shorts	2, 845 223, 767 251, 234	\$980, 217 14, 812, 871 5, 675, 752	\$344. 54 66. 20 22. 59	2, 890 199, 829 236, 741	\$1, 233, 184 15, 339, 128 6, 090, 971	\$426. 71 76. 76 25. 73	
Rock mined	477, 846 7, 712, 367 6, 366, 670	21, 468, 840	44. 93	439, 460 8, 233, 516 6, 795, 459	22, 663, 283	51.57	

# AFRICA

Southern Rhodesia.—The Shabani mine has been an important producer for many years and is probably producing at near maximum capacity. Other smaller mines add to the supply. Because of war restrictions, no figures of output have been released since May 1940.

Union of South Africa.—The Union of South Africa is unique in that it produces five kinds of asbestos-chrysotile, crocidolite, amosite, anthophyllite, and tremolite. The last two varieties are produced in small amounts, for local use only. Some years ago there was a large production of chrysotile from the Amianthus and Munnik Myburgh mines in the Kaapsche Hoop district of eastern Transvaal. The mines are now virtually worked out, but the loss from these sources is more than compensated by production from the recently developed Havelock mine in Swaziland, which has an annual output exceeding 24,000 tons of high-grade fiber.

Although exports of amosite and blue asbestos were considerably higher in 1942 than in 1941, stocks at the mills were maintained at normal levels. Added equipment has increased mill capacity.

The best blue fiber (crocidolite) occurs in the Prieska and Kuruman districts of Cape Province, where the largest production is centered. A small output is obtained in the Pietersburg district of Transvaal. The workings are shallow, and the product is less desirable than the Cape blue.

The following table shows production during recent years. duction in 1942 exceeded all previous records.

Asbestos produced in the Union of South Africa, 1938-42, by sources

Year	Transvaal	Cape Province	Natal	Total	Total value <sup>1</sup>
1938	16, 505	6, 484	2 187	<sup>2</sup> 23, 176	£416, 401
1939	15, 827	6, 144	79	22, 050	517, 535
1940	21, 011	6, 381	(3)	<sup>3</sup> 27, 392	492, 125
1941	4 18, 028	4 5, 408	(3)	5 28, 000	(6)
1942	7 20, 440	7 5, 281		5 34, 000	(6)

1 Value of local sales plus value of exports.

2 Small production in Natal in December 1936 and in 1937 included in 1938 figures.
3 Data for Natal not available.
4 January to October, inclusive.

5 Preliminary.
6 Data not available.

7 January to September, inclusive.

The following table shows the tonnage of each variety produced from 1938 to 1942, insofar as data are available.

Asbestos produced in the Union of South Africa, 1938-42, by varieties and sources, in short tons

				\ '	
Variety and source	1938 1	1939 2	1940 2	1941	1942
Amosite (Transvaal) Chrysotile (Transvaal) Blue (Transvaal) Blue (Cape) Anthophyllite (Transvaal)	8, 793 5 5, 573 2, 326 6, 484	11, 299 <sup>5</sup> 612 3, 983 6, 144 12	17, 767 646 2, 520 6, 381 78	3 15, 886 3 1, 408 3 675 3 5, 408 3 59	4 18, 675 4 1, 469 4 231 4 5, 281
	23, 176	22, 050	27, 392	6 28, 000	6 34, 000

Data from Union of South Africa, Department of Mines, Monthly Reports.
 Data from Union of South Africa, Department of Mines, Quarterly Reports.

<sup>3</sup> January to October, inclusive. <sup>4</sup> January to September, inclusive. <sup>5</sup> Includes 187 tons in 1938 and 79 tons in 1939 produced in Natal.

6 Preliminary.

#### SOVIET RUSSIA

Nearly all the Russian asbestos produced originates in the Bajenova district of the Urals, where there are both mines and mills. No production statistics are available since 1938, when an output of 86,000 metric tons was reported. Under the third Five-Year-Plan, an expansion of production capacity to 220,000 metric tons a year was contemplated. Such an objective was expected to be attained The bulk of the output would, as heretofore, be used in domestic asbestos-products plants. Among world producers the Soviet Union stands next to Canada on a tonnage basis, but, like Canada, a large share of the output consists of the shorter grades.

ASBESTOS 1433

Canada's shorter grades find ready market in nearby United States, but in Soviet Russia the short fibers are consumed by large domestic asbestos-products manufacturing industries. The Russian industry probably has expanded greatly to provide brake bands and clutch facings for the Union's growing automotive transport system and to furnish gaskets, packings, and heat insulation for its numerous immense munition factories. Russian reserves are estimated at 18,000,000 tons of fiber.

#### OTHER COUNTRIES

In addition to the blue asbestos in Western Australia, mentioned under New Developments, other deposits have been discovered on the Australian Continent. A deposit of asbestos—probably chrysotile as it occurs in serpentine rock—has been found on the western shore of Macquarie Harbor about 18 miles from Strahan, Tasmania. The occurrences are conveniently situated for transport, being 4 miles from the Gordon River, which is navigable. Preliminary prospecting and testing have been conducted over an area of 300 acres.

Extensive occurrences of high-grade asbestos are reported on South Island, New Zealand, but are too inaccessible for development at present. Presumably, the necessary fiber will be obtained from Australian mines. One asbestos-cement-products plant is operated in New Zealand, and a second plant is contemplated because of a

shortage of roofing and other building materials.

Considerable interest has centered recently on asbestos occurrences in Latin America. Reference has been made under New Developments to a large deposit of chrysotile in Venezuela. A deposit of blue asbestos has been known for many years in Bolivia and has been worked in a small way at intervals, but the quality is inferior to that of African blue. Small tonnages of asbestos are produced in

Argentina for local use.

According to recent reports an asbestos-cement-products industry will soon be established in the State of Minas Gerais, Brazil. The factory presumably will be located at an asbestos mine that is about to be developed, but information regarding a more exact location is not yet available. A sample of the asbestos submitted to the Bureau of Mines appeared to consist of strong, flexible fibers of tremolite, but they were positively identified by the Geological Survey as anthophyllite. The occurrence of this variety of asbestos in fibers comparable in strength with chrysotile or high-grade tremolite is very unusual. Asbestos-cement board will be one of the chief products of the new factory; and, although anthophyllite found in the United States is unsuitable for such use, the Brazilian product seems to have suitable qualities. The entire output of the mine probably will be used in the local plant.

· Samples of chrysotile of good strength and flexibility were received by the Bureau of Mines in 1942 from a deposit reported to be in the

Department of Junin, Peru, on the eastern slope of the Andes.

During 1942 the Bureau of Mines received samples of fair-quality chrysotile asbestos from deposits in Mexico, somewhere in the vicinity of the Laredo-Mexico City highway. The asbestos-bearing rock is said to be an outcrop of serpentine 10 kilometers long and 1.5 kilometers wide, in which more than 20 fiber veins occur. Some of the samples

examined by the Bureau of Mines consisted of cross-fiber veins of spinning fiber comparable in quality with Canadian asbestos, except that they were stained and discolored. This condition probably was due to surface alteration.

Chrysotile asbestos was discovered in Turkey in 1934. According to Turkish authorities, the deposit is between Karakose and Kogizman in the vilayet of Agri. Because of remoteness and technical difficulties, it has not been developed. Short-fiber asbestos suitable only for asbestos-cement products and insulation is produced in small quantities in the Eskisehir region. It is reported that small shipments were made to Germany and Hungary in 1942.

A small output of asbestos was reported from the Macheria deposit, Algeria, in 1942. No information is available on the variety or quality

of the fiber.

Cyprus normally produces several thousand tons of short-fiber chrysotile a year, and as there is virtually no local market the entire output is exported. Shipping conditions were quite difficult in the Mediterranean Sea during 1942, and presumably the Cyprus industry has been relatively inactive. As no new data have been obtained, the table that appeared in Minerals Yearbook, 1941, has not been repeated in this chapter.

# BARITE, WITHERITE, AND BARIUM CHEMICALS

By CHARLES L. HARNESS AND K. G. WARNER 1

#### SUMMARY OUTLINE

	Page	1	Page
Summary	1435	Witherite	 1442
Salient statistics	1436	Production	 1442
Barite	1436		 1443
Crude	1436	_ Imports	 1443
Production	1436		1443
Prices	1438		 1443
Consumption World production	1438	Prices	 1446
World production	1439	Foreign trade	 1446
Ground (and crushed)	1440		
Sales	1440 1442		
PricesForeign trade			
roreign trade	1442	1	

#### SUMMARY

The war and other factors caused substantial declines in the use of barite in certain industries but fostered expansion in other ways, so that the net demand remained high. More crude barite was produced in 1942 (449,873 short tons) than during any previous year except 1941 (483,391 tons). The quantity of crude barite sold or used by producers in 1942—429,484 tons valued at \$2,673,002—was exceeded only by 1941 sales—503,156 tons valued at \$3,134,234.

The largest single loss in markets for ground barite was in rotary oil-well drilling muds, reflecting a general decline in well-drilling activity in the United States. Demand for drilling muds in Trinidad and Venezuela was active, but sufficient shipping space was not available to meet requirements. Consumption of barite for lithopone and blanc fixe manufacture also decreased, owing to the curtailed use of the finished products in paints and civilian white goods, such

as linoleum, oilcloth, and rubber goods.

The quantity of crude barite consumed in making barium chemicals reached an all-time high in 1942. However, the tonnage of chemicals produced declined slightly owing to the reduced output of lithopone, which requires less barite per unit weight than other barium chemicals. Sales of barium carbonate, principally for use in case-hardening steel and in preventing efflorescence in structural brick, increased substantially, as did sales of barium nitrate for flares and barium peroxide for hydrogen peroxide manufacture.

Imports of crude barite in 1942 were 4,680 short tons from Canada and Cuba compared with 456 in 1941, all from Cuba. Imports of witherite (from Great Britain) were 3,066 tons in 1942 compared with 4,790 in 1941. Exports of barite from the United States are not

reported separately.

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Salient statistics of the barite, witherite, and barium chemical industries in the United States, 1938-42

	1938	1939	1940	1941	1942
Sarite:					
Crude:					
Producedshort tons_	335, 433	365, 870	390, 462	409 201	440.000
Sold or used by producers:	000, 400	900,010	390, 402	483, 391	449, 873
Short tons	309, 663	383, 609	409, 353	503, 156	429, 484
Value: 1	000,000	200,000	200,000	300, 100	429, 404
Total	\$2,004,521	\$2, 344, 103	\$2, 596, 743	\$3, 134, 234	\$2,673,002
Average	\$6, 47	\$6, 11	\$6.34	\$6. 23	\$6. 22
Imports for consumption:		1	40.01	40.20	₩0. 22
Short tons	24,845	11, 588	7, 391	456	4,680
Value: 2			1		2,000
Total	\$151, 235	\$55, 985	\$41,342	\$2, 518	\$34,756
Average	\$6.09	\$4.83	\$5, 59	\$5, 52	\$7.43
Apparent new supply \$short tons	334, 508	395, 197	416, 744	503, 612	434, 164
Domestic percent	92.6	97.1	98.2	99.9	98. 9
Apparent new supply \$short tons Domesticpercent Reported consumption (total)				00.0	30. 3
short tons	364, 985	391, 683	404, 388	490, 833	449, 424
Ground (and crushed):		002,000	101,000	200,000	110, 121
Sold or used by producers:	3.5			A Landau Carlos	
Short tons	161, 422	170, 695	184, 390	234, 877	178, 765
Value	\$2, 786, 823	\$2, 902, 973	\$3,697,806	\$4,606,832	\$3,611,745
Imports for consumption:	4-,,	Ψ=, 00=, 0.0	φο, σοι, σοσ	ψ±, 000, 002	φυ, υπ, 140
Imports for consumption: Short tons	1,700	1,590	314		
Value.	\$15, 466	\$14,999	\$3, 299		
Vitherite:	420, 200	411,000	ψο, 200		
Imports for consumption: Short tons					
Short tons	2.115	3, 819	3, 584	4, 790	3,066
Value	\$43, 568			\$107, 238	\$60, 824
arium chemicals:	Ψ20, 000	401,100	Ψ10, 120	φ101, 200	φυυ, o.2·2
Sold or used by producers: 4					
Short tons	165, 680	183, 748	198, 201	245, 952	207, 434
Value		\$12, 791, 269		\$16, 949, 120	\$17, 678, 769
Imports for consumption:	·	Ψ12, 101, 200	φ12, 000, <del>1</del> 11	φ10, 9 <del>1</del> 9, 120	917, 078, 709
Imports for consumption: Short tons	4, 519	3, 205	191	317	365
Value	\$254, 874	\$172, 490			
Exports of lithonone:	4201,011	Ψ1.2, 400	φ9, 043	\$15,944	\$103, 156
Short tons	1,734	4,845	14, 298	91 507	17 020
Value	\$153, 567	\$392, 798	\$1, 112, 362	21, 527 \$2, 079, 229	17, 036 \$1, 732, 898

1 F. o. b. mine shipping point.

3 Declared value f. o. b. foreign market.

3 Barite sold or used by producers plus imports.

4 1938-41: To avoid duplication, the barium chemicals reported here do not include the output of firms that make these chemicals from such products as barium chemicals and imported barite and witherite purchased in the open market. 1942: Includes barium chemicals made from barium chemicals and imported barite and witherite purchased in the open market. The data have been adjusted to remove duplisation

#### BARITE

#### CRUDE

#### PRODUCTION

Total mine output of crude barite in 1942-449,873 short tons-was greater than in any previous year except 1941, when a record quantons—was mined. Excellent demand tity-483,391 mining activity at high levels in the Southern, Midwestern, and Western barite-mining districts throughout the year.

When imports of German barite began to decline in 1938, production in the Southern district (Alabama, Georgia, South Carolina, Tennessee, and Virginia) expanded to meet requirements on the East coast. These requirements totaled about 220,000 tons annually, including about 180,000 tons of domestic origin, chiefly from the Southern district, and about 40,000 tons of crude imported barite, mostly from Germany. The German barite found a ready market on the East coast despite an import duty of \$4 a ton. In meeting wartime demands, production of crude barite in the Southern district in 1942 exceeded all previous years except 1941. In the Midwestern district

(Missouri and Arkansas) production increased slightly, as losses in well-drilling-mud markets were compensated by increased demands of lithopone and barium chemical plants in Illinois and Missouri. Western district barite output declined slightly, owing to decreased use of barite in California well drilling, but requirements for the manufacture of barium chemicals at Modesto, Calif., remained substantial. Barite was produced in Nevada and New Mexico; the output in the latter State was held in stock.

Crude barite sold or used by producers in the United States, 1941-42, by States

	194	11	194	2
- State	Short tons	Value	Short tons	Value
Georgia	 104, 446 212, 718 104, 511 81, 481	\$553, 445 1, 337, 756 779, 565 463, 468	86, 636 146, 270 83, 291 113, 287	\$483, 261 943, 131 624, 584 622, 026
Other States 1	 503, 156	3, 134, 234	429, 484	2, 673, 00

<sup>&</sup>lt;sup>1</sup> 1941; Arkansas, California, Colorado, Nevada, South Carolina, Texas, and Virginia; 1942; Alabama, Arkansas, California, Nevada, South Carolina, and Virginia.

Hubbell<sup>2</sup> prepared interesting articles on two of the largest producers of barite in the United States—L. A. Wood Co., Sweetwater, Tenn., and New Riverside Ochre Co., Cartersville, Ga. The L. A. Wood Co. operates seven open-pit mines in the Sweetwater districtthe Stephens, Harmon, Garrison, Pond Creek, Fork Creek, Roy, and Calhoun. Each of the mines has its own washing plant, including log washers and jigs. The output of the mines is accumulated at a railroad yard for loading. The yard is equipped with a kiln for decrepitating some of the material to facilitate screening out iron oxide, thus yielding a purer product for glass use. The firm, under the name of the Barytes Mining Co. (Cartersville, Ga.), also mines barite from an open pit in north Georgia. Two grades of barite are produced at the Georgia mine—one about 96 percent barium sulfate, the other about

New Riverside Ochre Co. mines barite from five open pits in the Cartersville (Ga.) area. The crude material is dug with five caterpillar-mounted shovels and moved from the pits to the plant in trucks. Overburden ranges from a film to over 60 feet. Working benches are operated at about 15 feet. Approximately 8 tons of barite-bearing material are needed to produce 1 ton of washed barite. Treatment at the washing plant includes log washing, screening, crushing, jigging, and tabling. Three grades are produced: (1) A low-grade product containing about 92 percent barium sulfate and 5 percent iron oxide for use in oil-well drilling muds; (2) a 96-percent grade, maximum 1.0 percent iron oxide, for lithopone manufacture; and (3) glass grade, 98 percent barium sulfate, maximum 0.3 percent iron oxide. In making the glass grade, iron oxide is removed by magnetic separation. Zapp 3 examined barite occurrences in the Llano (Tex.) area and

<sup>2</sup> Hubbell, A. H., Barytes—Nonmetallic Product of Eastern Tennessee: Eng. and Min. Jour., vol. 144, No. 1, January 1943, pp. 63-65. New Riverside—Producer of Barytes in Georgia: Eng. and Min. Jour., vol. 143, No. 10, October 1942, pp. 62-65.

<sup>3</sup> Zapp, Alfred, Barite in Northern Llano County: University of Texas Mineral Resource Survey Circ. 35, September 25, 1941, 6 pp.

found that, although barite did not appear to occur commercially in the locality, core drilling might reveal larger deposits.

#### PRICES

The opening 1942 quotation for crude barite from Georgia was \$8 a long ton, f. o. b. mine, rising to \$9 in April 1942, according to E&MJ Metal and Mineral Markets. From 1935 to 1940 the price was \$7 a long ton. Missouri crude barite, 93 percent BaSO<sub>4</sub>, was quoted at \$6 to \$6.35 a long ton, f. o. b. mine, in January 1942, rising to \$6.75 to \$7.25 a long ton in April. Missouri crude, 95 percent BaSO<sub>4</sub>, maximum 1 percent iron oxide, was quoted at \$6.25 to \$7.00 a long ton in January but rose to \$7 to \$7.50 in April.

The average value, f. o. b. mine shipping point, of crude barite for the entire United States, as shown by compilations from reports to the Bureau of Mines, was \$6.22 in 1942 compared with \$6.23 in 1941.

#### CONSUMPTION

Crude barite (domestic and imported) used in the manufacture of ground barite and barium chemicals in the United States, 1938–42, in short tons

	In manufacture of-	In manufacture of—					In m		
Year	Ground barite 1	Litho- pone	Barium chemi- cals	Total	Year	Ground barite 1	Litho- pone	Barium chemi- cals	Total
1938 1939 1940	193, 728 192, 112 200, 899	117, 007 141, 556 136, 885	54, 250 58, 015 66, 604	364, 985 391, 683 404, 388	1941 1942	243, 846 200, 443	153, 982 144, 821	93, 005 104, 160	490, 83 449, 42

<sup>1</sup> Includes some crushed barite.

Crude barite (domestic and imported) used in the manufacture of ground barite and barium chemicals in the United States in 1942, by States

State	Product manufactured	Plants 1	Barite used (short tons)
West Virginia Kansas Maryland Pennsylvania Georgia New York Arkansas South Carolina Fennessee	Ground barite, lithopone, and chemicals.  dododododododo	6 6 1 1 3 1 1 1 2	68, 55 39, 20 60, 93 51, 77 228, 97
		41	449, 42

A plant producing more than 1 product is counted but once in arriving at State totals.
 Includes some crushed barite.

#### WORLD PRODUCTION

Canada.—Barite output more than doubled in 1942 over 1941.4 Of the total production, 16,667 short tons, Nova Scotia produced 14,849 and British Columbia 1,818. The Nova Scotia mine, at Walton, Hants County, is comparatively new, having begun shipments It is operated by Canadian Industrial Minerals, Ltd., a subsidiary of Springer Sturgeon Gold Mines, Ltd. According to The Northern Miner,5 the firm ships most of its output to Trinidad for oil-well drilling mud. About two-thirds of the Nova Scotia sales is The British Columbia ground barite and the remainder crude barite. deposit is 23 miles southeast of Golden; most of the output is shipped to a grinding plant at Montreal. The deposit has been known for a number of years, but until recent road construction was undertaken by the British Columbia Government it was inaccessible to trucks. Trenching indicates a large tonnage of a pure white barite, analyzing about 98 percent barium sulfate.

Cuba.—Shipments of barite from Cuba, going mainly to Trinidad and the United States, declined somewhat in 1942 compared with 1941,6 probably owing to lack of shipping space. Cuban barite is produced in the Provinces of Oriente and Pinar del Rio. The latter area is the chief source, as the Oriente deposits are somewhat inacces-

The Cuban output is ground at Regla near Habana.

Eire.—Barite is mined in western Ireland from a vertical fissure vein about 7 feet wide that cuts Carboniferous limestone, it is reported.7 Benbulben Barytes, Ltd., operating the mine, ships crude, ground, and micronized barite, principally to Great Britain for use in lithopone manufacture and as a paint extender. The material analyzes about 96 to 98 percent barium sulfate, the impurities being chiefly silica.

Germany.—Before 1939 Germany was the chief producer of barite, supplying nearly half the world output. German production in 1937 was 452,388 and in 1938, 480,877 metric tons. Subsequent data are not available, but loss of export markets for crude and ground barite and barium chemicals has probably curtailed current output. Prussia is the chief producing State, followed by Baden. The barite occurs chiefly in veins and is recovered by underground mining.

Italy.—Annual production, which comes from about 40 deposits, is said to exceed 50,000 tons. The principal workings are near Trent, on the Island of Sardinia, in the Val D'Aosta, in Valassina, and in

Tuscany.

United Kingdom.—Production of barite in the United Kingdom has increased greatly since 1939, owing mainly to cessation of imports from Germany. Large deposits of barite are available in Ayrshire, Devonshire, Shropshire, and Derbyshire, but it is said that production cannot meet demand.

Much witherite is substituted for barite in England (see Witherite

section of this chapter).

<sup>4</sup> Canadian Mining Journal, vol. 64, No. 2, February 1943, pp. 60-61.

Northern Miner, vol. 29, No. 6, April 29, 1943, p. 17.

Bureau of Mines Mineral Trade Notes, Confidential Series 7, January 1943, p. 17.

Bureau of Mines Mineral Trade Notes, Confidential Series 2, August 1942, pp. 23-24. Confidential Series 4, October 1942, p. 24.

Chemical and Engineering News, vol. 20, No. 7, April 10, 1942, p. 467.

# World production of barite, 1937-42, by countries, in metric tons 1

[Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
Algeria	2, 137	3,069	(2)	(2)	(2)	(9)
Argentina	-,	0,000	768	2,680	4, 174	(2) (2)
Australia:			100	2,000	4,174	(2)
New South Wales	_ 268	322	(2)	(2)	(2)	(9)
South Australia	2,736	2,909	(2) 3,886	(2) 3,672	(2) 3, 631	(2)
Tasmania		2,000	0,000	0,012	0,001	(2)
Victoria	-l 7i				(2)	
Brazil (exports)	600	(2)	(2)	(2) (2) (2)	(2) (2) (2)	(2)
Canada	- 000	(-)		307	(2)	(2) (2) (2) (2) (2) (2) 15, 120
Chosen	8, 400	(2)	(2) (2) (2)	(2)	6,043	15, 120
Cuba	3, 849	( )	10,000	10 105	(2)	(2)
Egypt	51	20	12,000	16, 105	13, 223	(2)
France	19,850			61	30	(2) (2) (2) (2) (2) (2)
Germany:	- 19,000	(2)	(2)	(2)	(2)	(2)
Austria	855	373	(9)	(m)	-	
Baden	21,653	36, 305	(2) (2)	<u>®</u> ®®®®®®®®®®®®®®®®®®®®®®®®®®®®®®®®®®®	(2) (2)	(2)
Bavaria	11, 832	26, 748			(2)	(2)
Prussia 3	410, 634	401, 906	(2)		(2)	(2)
Saxony	432	230	(2) (2) (2) (2) (2) (2)		(2)	(2)
Thuringia	6, 790	15, 315			(2)	(2)
Württemburg	192	10, 515			(2)	(2)
Greece		34,700		(2)	(2)	(2)
India, British	15, 941	8, 205	24,055	(2)	(2)	(2)
ndochina	15, 941	8, 205 50 -	9, 404		(2)	(2)
taly	45, 202		155	185	<u> </u>	0000000000000000
Norway	45, 202	48, 169	(2)	(2) (2)	(2)	(2)
Portugal	119			(2)	(2)	(2)
Southern Rhodesia	- 119	24 91	25	20	(2)	(2)
Spain	-	500	50	(2)	(2) (2)	(2)
SpainUnion of South Africa	570	491	8, 606	9, 936		(2)
United Kingdom	74. 485		439	691	4 1, 326	8 448
United States	327, 380	77, 543 304, 298	(2) 331, 910	(2) 354, 219	(2) 438, 523	(2)

In addition to the countries listed, barite is produced in China, Czechoslovakia, Eire, Japan, and U. S. S. R., but data on production are not available.
 Data not available.
 Official figures which, it is reported, cover only output of mines included under the mining law.
 January to October, inclusive.
 January to September, inclusive.

#### GROUND (AND CRUSHED)

#### SALES

All principal uses of ground (and crushed) barite sold or used by producers declined in 1942, and the total, though comparing favorably with pre-1940 output, was 24 percent less than the record 1941 sales. In its individual consumption outlets, demand for use in well drilling dropped 24 percent, in paint 40 percent, in glass 3 percent, and in rubber 35 percent.

Ground (and crushed) barite sold or used by producers in the United States, 1938-42

	1938	1939	1940	1941	1942
Plants Short tons Value	161, 422 \$2, 786, 823	13 170, 695 \$2, 902, 973	184, 390 \$3, 697, 806	234, 877 \$4, 606, 832	19 178, 765 <b>\$3</b> , 611, 745

Ground (and crushed) barite sold or used by producers, 1940-42, by consuming industries

	19	40	19	<b>141</b>	19	42
Industry	Short	Percent	Short	Percent	Short	Percent
	tons	of total	tons	of total	tons	of total
Well drilling Paint. Glass Rubber Undistributed	138, 055	75	154, 760	66	117, 380	66
	11, 056	6	31, 009	13	18, 484	10
	12, 697	7	22, 615	10	21, 895	12
	4, 283	2	9, 800	4	6, 334	4
	18, 299	10	16, 693	7	14, 672	8
	184, 390	100	234, 877	100	178, 765	100

Virtually all barite is ground or crushed before use, but "ground (and crushed) barite" is generally held to mean barite ground for use other than in barium chemicals or lithopone, and such meaning is adhered to in this chapter. Nearly all ground barite is used for its physical rather than its chemical properties, except for the quantity consumed in glass batches.

As in years past, rotary oil-well drilling muds absorbed the greater part of the ground-barite output in 1942, although the number of wells drilled was considerably less than in 1941. The following table shows the relation between wells drilled, and ground barite consumed

in drilling muds.

Ground barite consumed in drilling wells in the United States, 1938-42

•	Wells		parite used t tons)	<b>V</b>	Wells		Ground barite used (short tons)	
Year	drilled 1	Total	Per well drilled	Year	drilled 1	Total	Per well drilled	
1938 1939 1940	26, 712 25, 987 28, 124	126, 697 125, 560 138, 055	4. 74 4. 83 4. 91	1941 1942	29, 070 17, 934	154, 760 117, 380	5. 32 6. 55	

<sup>&</sup>lt;sup>1</sup> Oil, gas, and dry wells drilled in United States, as recorded in chapters of this series on Crude Petroleum and Petroleum Products,

Barite has several functions in drilling muds, the principal one being to confine gas and oil to their respective formations during drilling. Barite drilling muds also seal the walls of the hole and lubricate the

drilling mechanism.

Foreign demand for barite drilling muds has expanded considerably since 1938, particularly in Trinidad and Venezuela. American, Cuban, and Canadian producers competed in these markets in 1942. The Southern and Midwestern districts generally supply most of the ground barite exported from the United States for well drilling, shipping 10,000 to over 20,000 tons annually, depending on foreign demand, through Mobile, Ala., New Orleans, La., and other Gulf ports.

One of the newer uses for crushed barite is in glassmaking, where it acts as a flux in the glass batch, permitting lower furnace temperature or increased output at the usual temperature. Barium compounds, particularly precipitated barium carbonate, are used in optical, bottle, and flat glasses, not only as fluxes but to impart density and brilliance to the finished product. As barium glasses corrode

ordinary glass pots, special types of pots are generally required. cording to a communication received by the Bureau of Mines from a large glass producer, the specifications of glass-grade barite are somewhat as follows: Barium sulfate, not less than 96 percent; moisture, not over 3 percent; iron oxide, not over 0.4 percent; titanium oxide, not over a trace; no particles coarser than 16-mesh; not over 3 percent plus 20-mesh; not over 40 percent minus 100-mesh; not less than 15 percent minus 100-mesh.

Ground barite has certain advantages as a paint extender. low oil absorption and fair sanding properties and contributes to a dense, nonporous film. Barite is added to inside paints to aid easy working with the brush; owing to the low oil absorption, considerable quantities can be incorporated without bodying. Its low tinting strength

makes it a good base for colored as well as white pigments.

Ground barite is also used as a filler for paper, paper board, wallpaper, rubber goods, linoleum, and oilcloth. A recent novel use is in weighting concrete ballast for drydock caissons. Barium cements containing as much as 50 percent barium oxide have high specific gravity. This suggests their possible use, in conjunction with such heavy aggregates as barite, in making heavy concrete blocks to be substituted for pig iron in ships' ballast.

The price quoted in Chemical Industries for ground barite, carlots, 350-pound barrels, works, was \$27.65 a short ton in 1942, the same as in 1941.

#### FOREIGN TRADE

There were no imports of ground barite in 1941 and 1942. ports for 1938-40 are shown in the salient statistics table of this chapter. Exports of ground barite are not reported separately.

#### WITHERITE

#### PRODUCTION

The Baroid Sales Division of the National Lead Co., which operates a mine near El Portal, Calif., is the only producer of witherite in the United States. Figures on output are not available for separate publication but are combined with those of barite.

Deposits of witherite in North America were reviewed in the

chapter of this series in Minerals Yearbook, 1941.

Nearly the entire world production of witherite is centered in northern England. Sources, preparation, and uses of witherite have been reviewed by Muddiman 9 and Michell. 10 Jameson 11 reviewed methods of analyzing witherite.

In British paint formulas, ground witherite has been substituted for ground barite for mixing with ultramarine blue to make a green pigment, and it is claimed that such substitution improves the product.<sup>12</sup>

<sup>Muddiman, E. W., Witherite: Jour. Oil Col. Chem. Assoc., vol. 25, 1942, pp. 127-142; British Chem. and Physiol. Abs., B, I, III, October 1942, p. 416.
Michell, F. B., Barite and Witherite: Mine and Quarry Eng., vol. 7, 1942, pp. 37-40, 44; Chem. Abs., vol. 36, No. 11, June 10, 1942, p. 3123.
Jameson, F. L., Examination of Natural White Pigments: Paint Mfr., vol. 12, 1942, pp. 145-146, 153; Chem. Abs., vol. 36, No. 21, November 10, 1942, p. 6817.
Bureau of Foreign and Domestic Commerce, Foreign Commerce Weekly, vol. 9, No. 10, December 5, 1942 p. 32.</sup> 

<sup>5, 1942,</sup> p. 33.

このないのは、大きのではないないではないのであるというないのであるというできましています。

#### PRICES

According to Chemical Industries, the price of ground witherite in 1942 remained constant at \$43 a short ton in carlots, bags, works, for the 90-percent grade, the same price as in 1941.

#### IMPORTS

Receipts of witherite were 3,066 short tons valued at \$60,824 in 1942, all from Great Britain, compared with 4,790 tons valued at \$107,238 in 1941. Exports of witherite, if any, are not reported separately.

Witherite, crude, unground, imported for consumption in the United States, 1938-42 [Value at port of shipment]

	Year	Short tons	Value	Year	Short tons	Value
1938 1939 1940		2, 115 3, 819 3, 584	\$43,568 64,106 70,126	1941 1942	4, 790 3, 066	\$107, 238 60, 824

#### BARIUM CHEMICALS

#### SALES

War conditions increased the demand for certain barium chemicals in 1942 but curtailed the production of others, particularly those whose principal uses were closely connected with civilian consumption.

whose principal uses were closely connected with civilian consumption.

All barium chemicals in the United States are derived from barite, except a small quantity obtained from witherite. Barite is crushed and roasted with coal, coke, or petroleum-coke breeze in a rotary kiln for

Barium chemicals sold or used by producers in the United States, 1938-42 1

Chemical	1938	1939	1940	1941	1942
Lithopone: 2					
Plants	11	11	11	9	40- 000
Short tons	125, 746	142, 759	151,802	176, 642	137, 320
Value	\$9,975,012	\$10, 461, 102	\$10, 197, 897	\$12, 550, 193	\$10,828,924
Blanc fixe (precipitated barium sulfate):	1 _				_
Plants	7	6	6	6	5
Short tons	19, 428	18, 653	22, 247	29, 352	21, 278
Value	\$921, 203	\$898, 198	\$1, 250, 303	\$1,806,882	<b>\$1,403,689</b>
Artificial barium carbonate (chemically			i .	1	
precipitated):			i		
Plants	4	5	5	5	7
Short tons	9, 543	12,478	13, 339	17, 477	18, 174
Value	\$459,901	\$617,799	\$616, 331	\$785,486	\$1,012,522
Other barium chemicals: 2	1	1	;		l .
Plants	5	7	7	7	11
Short tons	10, 963	9,858	10, 813	22, 481	30,662
Value	\$728,896	\$814,170	\$803,886	\$1,806,559	\$4, 433, 634
Total barium chemicals:	1	1	i		
Short tons	165, 680	183, 748	198, 201	245, 952	207, 434
Value	\$12,085,012			\$16, 949, 120	\$17, 678, 769

<sup>1 1938-41:</sup> To avoid duplication, the barium chemicals reported here do not include the output of firms that make these chemicals from such products as barium chemicals and imported barite and witherite purchased in the open market. 1942: Includes barium chemicals made from barium chemicals and imported barite and witherite purchased in the open market. The data have been adjusted to remove duplication.

<sup>2</sup> Does not include cadmium lithopone.

3 Figures cover chemicals, in order of value, as follows: 1938: Chloride, dioxide, sulfide, hydroxide, and oxide; 1939: Chloride, dioxide, hydroxide, sulfide, and oxide; 1940: Chloride, dioxide, hydroxide, sulfide, oxide, and nitrate; 1941: Chloside, sulfide, dioxide, hydroxide, and oxide, and tribarium aluminate; 1942: Nitrate, 11,489 tons, \$2,483,115; chloride, 13,414 tons, \$960,876; dioxide, 2,844 tons, \$666,232; hydroxide, 2,335 tons, \$267,672; sulfide and oxide, 580 tons, \$55,839.

about 4 hours, yielding black ash, which contains about 80 percent barium sulfide. The black ash is leached with hot water to give barium sulfide liquor. There were 21 producers of black ash in 1942, compared with 18 in 1941. The Bureau of Mines does not report the output of black ash, as this is regarded as an intermediate barium chemical. Where possible only finished barium chemicals not used in

the manufacture of other barium chemicals are reported. Production of lithopone, long a major outlet for barite, declined in

1942 to 137,320 short tons, the lowest figure since 1938. were nine producers in 1942, as in 1941. Paint remained the largest use of lithopone, but increasing military uses of paint did not compensate for losses in civilian paint markets caused by reduced construction of civilian dwellings and the shortage of painters for general maintenance work. Lithopone paint markets were also said to have been adversely affected by a growing use of titanium pigments in the white-pigment field. Shortages of linseed and other drying oils used with lithopone in the manufacture of linoleum and oilcloth held down production of these two commodities, which ordinarily consume 17,000 to 20,000 tons of lithopone annually. The declining production of rubber white goods has forced a corresponding decrease in the amount of lithopone needed for this purpose.

Lithopone 1 sold or used by producers, 1940-42, by consuming industries

	19	40	19	41	1942		
Industry	Short	Percent of total	Short tons	Percent of total	Short tons	Percent of total	
Paints, enamels, and lacquers. Floor coverings and textiles. Rubber. Other.	117, 075 18, 738 3, 387 12, 602	77 13 2 8	132, 691 21, 114 3, 547 19, 290	75 12 2 11	109, 216 45, 775 1, 047 11, 282	80 11 1	
	151, 802	100	176, 642	100	137, 320	100	

<sup>1</sup> Does not include cadmium lithopone.

Manufacturers of lithopone generally purchase washed and jigged barite analyzing about 96 percent barium sulfate, 1 to 2 percent Fe<sub>2</sub>O<sub>3</sub>, less than 1.75 percent silica, and no more than traces of zinc, lead, and fluorides. The barite is crushed and roasted with coal to form black ash as described above. The solution of barium sulfide obtained from black ash is reacted with a solution of zinc sulfate, whereby lithopone (barium sulfate intimately mixed with zinc sulfide) is precipitated; it is then dried, roasted, quenched in water, ground, bagged, and sold.

Lithopone has been suggested as a carrier pigment for luminous

paints.13

The demand for blanc fixe declined owing to curtailment in use of white paint, rubber goods, linoleum, and oilcloth, its major outlets. Blanc fixe is made by reacting a solution of sodium sulfate with a solution of barium sulfide, precipitating barium sulfate (blanc fixe) and leaving a valuable byproduct—sodium sulfide—in solution. Blanc fixe is also a byproduct of the manufacture of hydrogen peroxide by the barium peroxide-sulfuric acid process. Five producers of

<sup>18</sup> Chemical and Engineering News, vol. 20, No. 8, April 25, 1942, p. 529.

blanc fixe reported to the Bureau of Mines in 1942 compared with six in 1941.

Barium carbonate production expanded to meet added demands in several fields. There were seven producers in 1942, five in 1941. This barium chemical is generally made by adding a solution of soda ash to one of barium sulfide, thereby precipitating insoluble barium carbonate, leaving byproduct sodium sulfide in solution. Probably the most important direct wartime use of barium carbonate is in salt baths for case-hardening bomb shells, tools, and other steel parts. Before the war witherite, being less costly, was employed for this purpose rather than precipitated barium carbonate; however, reduced imports of witherite have broadened, at least temporarily, the demand for the synthetic material. The action of barium carbonate as a carbon carrier in steel hardening is not precisely known, but when it is mixed with powdered coke and heated with iron parts at 1,700° F., the coke is gradually oxidized and the carbon content of the surface grains of the iron is increased, thus case-hardening the product. Other barium compounds, notably barium peroxide, are said to be capable of similar use. Barium carbonate is an intermediate in the manufacture of certain other barium chemicals, particularly barium peroxide and barium nitrate. In making the peroxide, barium carbonate is calcined with coke, yielding the oxide, which is then heated with air or oxygen under pressure, yielding a mixed barium peroxide-oxide. The percentage of peroxide obtained depends on the efficiency of the process used. Although most hydrogen peroxide is today made by electrolytic oxidation methods, substantial quantities of barium peroxide are still used to make hydrogen peroxide. There were three producers of barium peroxide in 1942, two in 1941. Barium carbonate can be used in glassmaking, as previously mentioned. The carbonate and other barium compounds are used in brickmaking to prevent formation of scum.

Barium nitrate is generally obtained by treating the carbonate with The nitrate is used in green signal flares and in explonitric acid. sives. In 1942, five firms reported production of barium nitrate compared with three in 1941.

Barium chloride, which may be crystallized from a solution of barium sulfide and calcium chloride, is used to purify salt brines for chlorine and sodium hydroxide manufacture, in making coatings for photographic paper, in the manufacture of extended titanium pigments, in color lakes, in finishing white leather, and in purifying beetsugar juice. Three firms produced barium chloride in 1942, as in 1941.

Barium hydroxide was produced by four companies in 1942 (four in 1941), principally for use in beet-sugar purification and for refining animal and vegetable oils.

PRICES

#### Range of quotations on barium chemicals, 1940-421

	1940	1941	1942
thopone: Domestic, ordinary, delivered, bagspound. Dobarrelsdo High strength, bagsdo	\$0.03¾ .03¾ .05		
Dobarrels	. 0514 . 0514 . 0514	.051/4056	
worksshort ton_ rium chlorate, 112-pound kegs, New York pound_ rium chloride, barrels, delivered zone 1 short ton_ rium dioxide (binoxide or peroxide), 88 percent,	\$45.00 -62.50 .2045 77.00 -92.00	45.00 -65.00 .45 77.00 -92.00	\$55. 00 -65. 00 .60 77. 00 -92. 00
drumspound	.1012 .05½07 .09½10½	.05½07 .08½12½	.0607 .10½12½

<sup>&</sup>lt;sup>1</sup> Chemical Industries (formerly Chemical Markets), New York (monthly). <sup>2</sup> Lowest price for pulp grade, highest for high-grade precipitated.

#### FOREIGN TRADE

# Barium chemicals imported for consumption in the United States, 1938-42 [Value at port of shipment]

Year	Lit	thopone		Barium	dioxide	cipi	cipitated barium sulfate)			Barium carbonate (precipitated)	
	Short tons	Va	lue I	Pounds	Value	Shor		lue	Short tons	Value	
1938	3, 93 2, 64		, 121 , 893	100 350	\$13 51			102	(1)	\$32	
1941 1942	(2)		9	4,032	208		15 28 1,	865 357			
Year	Barium rid		Bariun	n nitrate		m hy- xide	Bariur	n oxide	por	m com- inds e. s.)	
	Short tons	Value	Short tons	Value	Short tons	Value	Pounds	Value	Short	Value	
1938	39	\$2,351 1,329	100 18	\$12,061 11,094 1,427	360 151 292	\$16, 874 19, 975 3, 332 10, 791	22	\$13	22	\$11, 320 7, 244 4, 286 4, 071	
1942	36	15, 770	(3)	1	147	9, 361			154	76, 667	

<sup>1 110</sup> pounds.

#### Lithopone exported from the United States, 1938-42

Year	Short	Va	alue	Year	Short	Va	lue
	tons	_ Total	Average	i ear	tons	Total	Average
1938 1939 1940	1, 734 4, 845 14, 298	\$153, 567 392, 798 1, 112, 362	\$38. 56 81. 07 77. 80	1941 1942	21, 527 17, 036	\$2,079, 229 1,732,898	\$96. 59 101. 72

<sup>2 112</sup> pounds

<sup>53</sup> pounds.

#### **POTASH**

#### BY BERTRAND L. JOHNSON AND K. G. WARNER

#### SUMMARY OUTLINE

	Page		Page
General conditions	1447	Consumption	1451
Salient statistics	1448	Review by States	. 1452
Production and sales	1449	Foreign trade	<b>1455</b>
Prices			

#### GENERAL CONDITIONS

Production and sales of domestic potassium salts continued to increase in 1942, with a record output of over a million and a quarter short tons of marketable potassium salts (1,267,455 short tons) containing 679,206 tons of equivalent  $K_2O$ . (See fig. 1.) The still




FIGURE 1.—Production of marketable potassium salts in the United States, 1933-42.

larger quantity sold (1,277,317 tons) carried 680,831 tons of equivalent potash  $(K_2O)$ . Stocks in producers' hands at the close of the year continued to decline. Exports considerably exceeded imports. Domestic consumption was the highest on record—about 628,000 tons of  $K_2O$ . For the second year the United States has proved itself to be self-sufficient as to potash.

American potash producers are reported to have sold virtually their entire output to March 1943 early in 1942. Late in 1942,

The state of the s

不是一人在你不是一个一个一个人的人的人,我们就是我们的一个人的人的人

according to trade journals, efforts of consumers, who had not adequately covered their requirements in the preceding spring, to obtain additional supplies created a tight market, which was alleviated irregularly by imports of muriate of potash from the U.S.S.R. on a lend-lease assignment to the Defense Supplies Corporation.

To assure equitable distribution of available domestic potash from producers to their immediate customers, largely the fertilizer companies, the War Production Board, on February 27, 1943, placed the distribution of domestic potash salts (muriate of potash, sulfate of potash, sulfate of potash-magnesia, and run-of-mine potash) under allocation control (General Preference Order M-291). This order was based upon the claim that the requirements for the defense of the United States had created a shortage in the supply of potash for defense, for private account, and for export. The order, effective April 1, 1943, covers three allocation periods: (1) April and May 1943, (2) the following 10 months, and (3) April and May 1944.

German control of a considerable part of the domestic potash

production was exposed late in 1942.

General discussions of the domestic potash industry by Turrentine 1 and Kieffer <sup>2</sup> appeared in 1942. In 1943, a new book by Turrentine <sup>3</sup> described the development of the American potash industry since 1926 and supplemented his earlier book. Domestic reserves of potash were described by Mansfield.<sup>5</sup>

Salient statistics of the potash industry in the United States, 1940-42

		1940	1941	1942
Production:				
Potassium salts (marketable)	about toma	070 040	000 450	
Approximate equivalent, K <sub>2</sub> O	snort tons			
			524, 875	679, 206
Potassium salts	do	6777 000	004.040	1 077 014
Approximate equivalent, K <sub>2</sub> O	do	677, 892		1, 277, 317
Value at plant		393, 058	531, 346	680, 831
Value at plant Average per ton		\$12, 562, 050 \$18, 53	\$17, 368, 237	\$22, 962, 518
Imports:		\$10.00	\$17.46	\$17. 98
Fertilizer materials	short tone	274, 473	49, 337	15 005
Approximate equivalent, K <sub>2</sub> O	до. спои изопа	115, 241	13, 185	15, 895
Value		\$5, 148, 852	\$1,023,927	2, 915 \$418, 787
Value	short tons	14. 564	12, 918	5, 433
Approximate equivalent, K.O.	do	3, 449	2, 633	1, 444
Value		<b>\$2, 411, 919</b>	\$4, 702, 971	\$1, 784, 674
Exports:			Ψ±, 102, 011	φ1, 101, 011
Fertilizer materials Approximate equivalent, K <sub>2</sub> O	short tons	93,060	91, 950	84, 402
Approximate equivalent, K <sub>2</sub> O	do	55, 836	50, 573	50, 641
Value		\$3, 141, 170	\$2, 592, 697	\$2, 184, 044
Value	short tons	14, 180	12, 883	13, 306
Approximate equivalent, K <sub>2</sub> O	do	7,000	6,300	6, 500
		\$3,096,909	\$2, 972, 137	\$3,611,294
Consumption:			. , ,	<b>4-,</b> ,
Apparent consumption: 1				
Potassium salts	short tons	859, 689	952, 265	1, 200, 937
Approximate equivalent, K <sub>2</sub> O <sub></sub>	do	448, 912	490, 291	628, 049
Actual sales for consumption:	· ·	,	· /	,
Approximate equivalent, K <sub>2</sub> O	do	449, 376	490, 531	627, 294
		· ·	· '	•

<sup>&</sup>lt;sup>1</sup> Quantity sold by producers, plus imports, minus exports.

<sup>1</sup> Turrentine, J. W., Wartime Contribution of the American Potash Industry: Ind. and Eng. Chem., ind. ed., vol. 34, No. 12, December 1942, pp. 1422-1426.

2 Kieffer, D. C., Potash (in 1941): Mineral Ind., vol. 50, 1942, pp. 445-461.

3 Turrentine, J. W., Potash in North America: Am. Chem. Soc. Mono. Ser., Reinhold Publishing Corporation, New York, 1943, 186 pp.

4 Turrentine, J. W., Potash: A Review, Estimate, and Forecast: John Wiley & Sons, New York, 1926,

<sup>188</sup> pp.

Mansfield, G. R., American Potash Reserves: Ind. and Eng. Chem., ind. ed., vol. 34, No. 12, December 1942, pp. 1417-1421.

#### PRODUCTION AND SALES

Domestic production of marketable potassium salts has increased each year since 1934, recent annual increments being much larger than those in the earlier years (see figure 1); in 1941 a 50-percent increase is shown over 1940, and in 1942 a 28-percent increase over 1941. Production in 1942 was 1,267,455 short tons, with an average  $K_2O$  content of 55.59 percent, compared with 53.21 percent  $K_2O$  reported for 1941. Production of equivalent potash ( $K_2O$ ) in 1942 exceeded that of 1941 by 154,331 tons. Sales of potassium salts were over a million and a quarter tons in 1942 and contained 680,831 tons of equivalent potash ( $K_2O$ )—also a 28-percent increase over 1941. Sales exceeded production in 1942, and producers' stocks were drawn upon to meet the demand. The average value per ton of sales increased to \$33.73 in 1942 from \$32.69 in 1941. Production of 50 percent muriate was only a little larger than in 1941, but there was a 45-percent increase in the quantity of sulfate of potash and sulfate of potash-magnesia produced, as shown in the accompanying table of production by grades.

Potassium salts produced in the United States, 1941-42, by grades, in short tons

	1941	1942
Muriate of potash: 60 percent K <sub>2</sub> O minimum  50 percent K <sub>2</sub> O minimum  Manure salts, run-of-mine	663, 608 85, 398 154, 979	878, 997 85, 680 183, 404
Sulfate of potash and sulfate of potash-magnesia	986, 458	119, 374

The potash industry of the United States is overwhelmingly a western one, more than 99½ percent of the 1942 output in terms of K<sub>2</sub>O having come from California, New Mexico, and Utah. Nearly 81 percent of the equivalent potash (K<sub>2</sub>O) production came from the deeply buried Permian saline sedimentary deposits of New Mexico and 19 percent from the saline lake brines of California and Utah, whereas less than 0.5 percent was recovered as a byproduct of manufacturing processes (cement and distillery operations in Maryland). The potash salts sold in 1942 were largely refined or processed products.

The potash-producing companies in the United States in 1942 were: The American Potash & Chemical Corporation, 122 East 42d Street, New York City (plant at Trona, on Searles Lake, Calif.); United States Potash Co., Inc., 30 Rockefeller Plaza, New York City (mine and plant near Carlsbad, N. Mex.); Potash Company of America, Carlsbad, N. Mex. (mine and plant near Carlsbad, N. Mex.); International Minerals & Chemical Corporation, 20 North Wacker Drive, Chicago, Ill. (mine and plant near Carlsbad, N. Mex.); Bonneville, Ltd., 540 West Seventh South, Salt Lake City, Utah (plant near Wendover, Utah); North American Cement Corporation, 41 East 42d Street, New York City (plant at Security, Md.); and U. S. Industrial Chemicals, Inc., 60 East 42d Street, New York City (plant at Baltimore, Md.).

Potassium salts produced, sold, and in producers' stocks in the United States, 1938-42

	Production				Sales				Producers' stocks			
Year	Opera- tors	Potas- sium salts (short tons)	Equivalent as potash (K <sub>2</sub> O) (short tons)	Opera- tors	Potassium salts (short tons)	Equivalent as potash (K <sub>2</sub> O) (short tons)	Value f. o. b. plant	Opera- tors	Potas- sium salts (short tons)	Equivalent as potash (K <sub>2</sub> O) (short tons)		
1938 1939 1940 1941 1942	9 6 7 7 7	534, 945 546, 757 658, 249 986, 458 1, 267, 455	316, 951 312, 201 379, 679 524, 875 679, 206	9 6 7 7 7	498, 189 634, 014 677, 892 994, 843 1, 277, 317	286, 437 366, 287 393, 058 531, 346 680, 831	\$9, 748, 290 12, 028, 195 12, 562, 050 17, 368, 237 22, 962, 518	6 -5 7 7 7	158, 540 54, 233 35, 060 26, 374 14, 158	87, 440 29, 440 16, 370 9, 712 6, 041		

#### PRICES

The General Maximum Price Regulation (Federal Register, April 30, 1942, pp. 3153-3158), issued April 28, 1942, under authority vested in the Price Administrator by the Emergency Price Control Act of 1942 and effective May 11, 1942, fixed potash prices at their March 1942 maximum.

Price lists for the 1942-43 fertilizer season were released by the major potash companies on dates ranging from May 29 to June 15, 1942. Most of the new schedules applied to the 12 months from June 1, 1942, to May 31, 1943. The Potash Company of America, however, released a schedule for the 10 months June 1, 1942, to March The following base prices were reported by various pro-31, 1943. ducing companies.

Muriate of potash (62 to 63 percent), 62 percent K<sub>2</sub>O 53½ cents per unit K<sub>2</sub>O.

Muriate of potash, 60 percent minimum\_\_\_\_\_\_ 53½ cents per unit  $K_2O$ . Muriate of potash, granular (50 to 52 percent), 50 56 cents per unit  $K_2O$ . percent minimum. Manure salts:

22 percent K<sub>2</sub>O minimum 25 percent K<sub>2</sub>O minimum Sulfate of potash, 90 to 95 percent K<sub>2</sub>SO<sub>4</sub>—basis 90 \$36.25 per short ton.

--- 20 cents per unit K2O. 21 cents per unit K2O.

percent K2SO4. Sulfate of potash-magnesia, 40 percent K<sub>2</sub>SO<sub>4</sub> mini- \$26.00 per short ton. mum, 18.50 percent MgO.

Basing points for the New Mexico companies for muriate of potash were designated to be ex-vessel Atlantic and Gulf ports within the United States, and for the American Potash & Chemical Corporation ex-vessel principal continental United States ports. Prices for manure salts, where stated, were based upon Carlsbad, N. Mex., only. Sulfate of potash and sulfate of potash-magnesia prices quoted by the International Minerals & Chemical Corporation were ex-vessel Atlantic and Gulf ports within the United States. At buyers' option, muriate of potash could be purchased f. o. b. Carlsbad, N. Mex., at 11.2 cents per unit K2O below ex-vessel price, and f. o. b. Trona, Calif., for 8 cents per unit K2O below net ex-vessel price at Pacific coast ports.

Seasonal discounts offered by the Potash Company of America, the American Potash & Chemical Corporation, and the International Minerals & Chemical Corporation were 8 percent on orders accepted through June 30, 1942, for delivery in equal monthly installments from June 1, 1942, through March 1943, and 4 percent additional upon

1451 POTASH

では、これでは、100mm 100mm 1

completion of contracted deliveries; no discounts were allowed on orders placed after June 30, 1942. The United States Potash Co. allowed 8 percent discount from ex-vessel prices on orders placed for June delivery and on those placed before July 1, 1942, for equal monthly tonnage deliveries from June 1, 1942, to March 31, 1943, and 4 percent additional credit upon completion of contracted deliveries; on orders placed after June 30, 1942, but before October 1, 1942, for equal monthly tonnage deliveries from October 1, 1942, to March 31, 1943, it allowed 4 percent from ex-vessel prices and 2 percent additional credit upon completion of delivery of the contracted tonnage; no discounts were allowed on orders placed after September 30, 1942.

A 6-percent increase in freight rates went into effect in March 1942.

The Office of Price Administration requested potash producers to absorb that part of the increase necessary to maintain ex-vessel prices at the established level. Later, a 3-percent tax on the transportation of property was imposed by section 620 of the Revenue Act of 1942, and the potash companies were also required to absorb this increase in a similar manner. In both instances, however, the buyer was required to pay the increased charges on potash sold at f. o. b. Carlsbad

prices.

In February 1942, the Office of Price Administration issued a temporary order freezing retail prices of certain potash salts at levels prevailing from February 16 to February 20, 1942. These temporary price maximums were made permanent by Maximum Price Regulation 135 - Mixed Fertilizers, Superphosphate, and Potash (Federal Register, April 30, 1942, pp. 3187-3189), issued and effective April 28, 1942. The prices of muriate of potash, sulfate of potash, manure salts, or any other substance containing K<sub>2</sub>O when marketed or sold to consumers for use in growing crops and plants, and not for resale, were fixed at the above-mentioned February 1942 prices.

#### CONSUMPTION

In 1942 the United States and its possessions consumed potash salts containing approximately 628,000 short tons of K<sub>2</sub>O, which were largely, though not entirely, of domestic origin. The following table, in which information from various sources has been combined, indicates a domestic consumption of 627,294 short tons.

Apparent consumption, calculated by subtracting exports (57,141 tons) from the sum of imports (4,359 tons) and producers' sales (680,831 tons), was 628,049 tons of K<sub>2</sub>O in 1942. The difference in consumption figures obtained by these two methods is almost

negligible.

Apparent domestic consumption of potassium salts, in terms of equivalent potash (K<sub>2</sub>O), and its relationship to sales of domestic producers for a period of years are shown in figure 2.

A break-down of domestic deliveries of American potash by the major domestic producers according to use, as shown in the accompanying table, indicates that 90 percent in 1942 went to the fertilizer industry and 10 percent for chemicals. The picture is not quite complete, however, because no comparable break-down is available for imports or for sales of the minor domestic producers.




FIGURE 2.—Comparison of apparent domestic consumption of potash (K<sub>2</sub>O) and sales of domestic producers of potash in the United States, 1925-42.

Sales of primary potash in the United States for consumption and export, 1940-42, in short tons of  $K_2O$ 

	1940	1941	1942
Deliveries of potash of domestic origin by major companies, as from reports of American Potash Institute— In United States and possessions:			
Agricultural Chemical For export	321, 414	435, 940	558, 356
	37, 815	51, 531	63, 844
	23, 707	24, 807	37, 955
Imports for consumption plus sales of minor domestic producers	382, 936	512, 278	660, 155
	129, 276	35, 126	24, 280
Total exports	512, 212	547, 404	684, 435
	62, 836	56, 873	57, 141
Actual sales for consumption in the United States	449, 376	490, 531	627, 294

#### REVIEW BY STATES

California.—In 1942 the American Potash & Chemical Corporation (122 East 42d Street, New York City), only producer of potash in California, used the highly complex brine of Searles Lake, in the southeastern part of the State, as its raw material and produced both agricultural and chemical grades of potassium chloride, as well as potassium sulfate and potassium bromide, in its plant at Trona. Its total output of marketable potash salts was greater in 1942 than in 1941, when a long strike seriously affected production. Recent technical developments at the Trona plant are described by Robertson.<sup>6</sup>

nical developments at the Trona plant are described by Robertson.<sup>6</sup> German ownership of most of the capital stock and control of this company was disclosed by the Alien Property Custodian when he

<sup>6</sup> Robertson, G. R., Expansion of the Trona Enterprise. Plant of the American Potash and Chemical Corporation: Ind. and Eng. Chem., ind. ed., vol. 34, No. 2, February 1942, pp. 133-137.

POTASH 1453

announced, on October 20, 1942, the vesting in him of 90.79 percent of the capital stock of the company owned by German nationals. The property vested consisted principally of 474,726 shares, registered in the names of Consolidated Gold Fields of South Africa, Ltd., Gold Fields American Development Co., Ltd., New Consolidated Gold Fields, Ltd., and Administratickantoor Diligentia, all of which are beneficially owned by Wintershall A. G., Germany (dominant factor in the German potash industry) and Salzdetfurth A. G., Ger-

many (second-largest potash company in Germany).

Maryland.—In Maryland, two companies have for several years produced a few thousand tons of byproduct potash annually for agricultural use. One of these, the North American Cement Corporation (41 East 42d Street, New York City), recovered a few thousand tons of impure sulfate of potash from cement-kiln flue dust in 1942 at its Security plant near Hagerstown, Md. U. S. Industrial Chemicals, Inc. (60 East 42d Street, New York City), continued to manufacture a byproduct potash-bearing material by incinerating waste residue from distillation of industrial alcohol from fermented molasses at its Fairfield plant, Baltimore. Blackstrap molasses has been used as raw material for several years but is no longer available; therefore, it has become necessary to use grain as a substitute source of alcohol. All grain residues will be recovered as distillers' dried grains and sold as such; consequently, no potash will be recovered.

New Mexico.—Mine production of the Carlsbad potash district has been climbing steadily. In 1940 it passed 1,200,000 short tons of ore, in 1941 it reached 2,270,000 tons, and in 1942 the three companies operating in the area mined 3,035,549 tons of sylvinite and langbeinite with an average equivalent K<sub>2</sub>O content of 21.52 percent. All the companies mined sylvite (potassium chloride), and one—the International Minerals & Chemical Corporation— also mined langbeinite (a potassium-magnesium sulfate). The greater part of the production was sylvite, most of which was processed to yield 60 percent or higher-grade K<sub>2</sub>O muriate. Potassium sulfate and potassium-magnesium sulfate were produced from langbeinite by the International Minerals & Chemical Corporation in the refinery at its mine near Carlsbad. Potassium sulfate also was produced by the Potash Company of America at plants in Oklahoma and Texas; this company also produced potassium hydroxide and potassium chlorate from syl-

vite at a plant at its mine near Carlsbad.

The Union Potash & Chemical Co., the most recent company to undertake potash mining in the Carlsbad area, merged with its parent company, the International Minerals & Chemical Corporation (formerly the International Agricultural Corporation), March 31, 1942. On October 31, 1941, a contract was completed with the Defense Plant Corporation whereby magnesium chloride cell feed would be produced from a waste potassium-magnesium-bearing brine, containing about 16 percent magnesium chloride, by a process developed by the International Minerals & Chemical Corporation. The magnesium chloride will be obtained by evaporation and selective crystallization, and the dried product will be shipped to a magnesium-metal plant at Austin, Tex., operated by the International concern. The potash-bearing solution remaining after removal of the magnesium chloride will be returned to the potash refinery, and the potassium salts previously wasted will be recovered. The magnesium chloride plant was under construction in 1942.

At the Potash Company of America plant an additional 2,400-horsepower Diesel engine was recently installed. Late in 1942 a 5-year contract was reported to have been concluded between the company and the City of Carlsbad, whereby the city would drill a well and supply water to a point near the Bataan Bridge over Pecos River. The company will pump the water to its mine for domestic and industrial uses formerly supplied by tank haulage.

One effect of the war is the loss to the company of cocoanut-oil soap, its principal flotation agent and previously imported, but satisfactory substitutes are said to have been developed. The com-

pany electrolytic plant was inactive for part of the year.

Utah.—In Utah three types of potash occurrences are being exploited—potassium-bearing brines, hydrothermal deposits of the potassium sulfate alunite, and bedded deposits of the potassium chlorides carnallite and sylvite. Only the first type is in commercial production, but the alunite deposits are being developed intensively,

and the bedded chloride deposits are being tested.

Bonneville, Ltd. (540 West Seventh South, Salt Lake City), only potash producer in Utah in 1942, is obtaining potassium chloride from the potassium-bearing brine that saturates the thin, crystalline salt mass of Salduro Marsh, near the western edge of former Lake Bonneville in the Great Salt Lake Desert in northwestern Utah. The company output has increased each year since it began operating in 1938. Production was nearly 25 percent greater in 1942 than in 1941.

Interest in the alunite (a hydrous basic potassium aluminum sulfate) deposits of the Marysvale district, Piute County, has revived, particularly with regard to the aluminum content rather than the potassium content, which was considered more important during the First World War. Both vein and replacement alunite deposits The vein deposits lie in Alunite Ridge between the forks of Cottonwood Creek. The replacement deposits are more numerous and are distributed much more widely. Total reserves of both types exceed 11 million tons of pure alunite, of which the vein deposits account for only 1,336,600 tons. Mining operations in the Marysvale district in 1942 were concentrated at the White Horse mine (a replacement-type deposit) northeast of Marysvale, where an open-pit mine is being developed by Kalunite, Inc., Marysvale. Operations in 1942 comprised development work, preparation of the mine and crushing plant for production, road construction, completion of a bridge over Sevier River, and erection of buildings at the mine. The alunite ore will be sent to Salt Lake City for processing. None was treated in 1942, except in the laboratory. A plant to obtain alumina and potassium sulfate from alunite was being erected in 1942 in Salt Lake The Kalunite process to be used in this plant consists in (1) dehydrating the alunite, driving off the water of crystallization and then dissolving the product in dilute cyclic sulfuric acid and potassium sulfate solutions to form potash alum; (2) autoclaying the potash alum to a hydrous basic potassium aluminum sulfate; (3) calcining this sulfate to drive off sulfur oxides, thereby producing a mechanical mixture of alumina and potassium sulfate; and (4) leaching this soluble potassium sulfate from the insoluble alumina.

The Bureau of Mines carried out exploratory work (diamond drilling, trenching, test pitting, and sampling) on alunite deposits in the

<sup>&</sup>lt;sup>7</sup> Thoenen, J. R., Alunite Resources of the United States: Bureau of Mines Rept. of Investigations 3561, 1941, 48 pp.

1455 POTASH

vicinity of Marysvale in 1942 and early in 1943 but temporarily suspended it February 25, 1943. The work, which was done on the Mineral Products, Yellow Jacket, Close In, White Horse, and Winkleman claims, indicated a large tonnage of alunite.

A study of the beneficiation of the replacement (disseminated) alunites from this region is included in a report by Gabriel and Dasher.8

In the Grand County potash field of eastern Utah in 1942 a wellknown as Defense Plant Corporation-Utah Magnesium Corporation Reeder No. 1—was core-drilled by the Bureau of Mines with the cooperation of the Geological Survey, as agents for the financing Defense Plant Corporation, in the SE¼SW¼SE¼ sec. 4, T. 22 S., R. 19 E., about 7½ miles west-southwest of Thompson on the Denver & Rio Grande Railroad and about 1½ miles south of Crescent Junction. Material was moved on location May 1, 1942, and the well was spudded in on May 6 and completed August 3, 1942, at 4,207 feet.

The well is within the narrow, complexly strike-faulted zone along the crest of the long northwest-trending Salt Valley anticline, here plunging northwestward under Cretaceous cover. It started in the Cretaceous Mancos shale and bottomed in the Paradox formation of the Pennsylvanian (Carboniferous). The well shows an abnormal geologic section, possibly due to an upthrust of the plastic salt-bearing Paradox formation into the fault zone. About 3,000 feet of sediments of Jurassic, Triassic, Permian, and Pennsylvanian age, normally expected to be present in this well, are missing. The Paradox formation extended from 2,091 feet to the bottom of the well. The section between 3,318 and 3,588 feet contained 91.6 feet of carnallite with an average assay of 39.5 percent carnallite. Individual carnallite beds were 1 foot to 13.5 feet thick and assayed 10 to 80 percent carnallite. There were two sylvite sections, the first extending from 3,419 to 3,518 feet, with 42 feet of sylvite averaging 24 percent sylvite, and the second from 4,152 to 4,157.5 feet and containing 5.5 feet of sylvite with an average of 41.3 percent of the mineral.

The normal thickess of neither the salt series nor the potash beds in this region is known. The salt core shows folding, flowage, and widely varying abnormal dips of the salt, as would be expected in squeezed and upthrust plastic salt beds. The wells of the district give no definite proof of the thickness or potassium content of the undisturbed saline beds of the region and little information as to their

メージを見るというということに、

extent and distribution within the fault zone.

Late in 1942 the Potash Company of America (Carlsbad, N. Mex.) entered into a prospecting agreement with the Utah Magnesium Corporation, whereby the former is to drill a number of deep wells and to prospect the holdings of the latter company near Crescent Junction on which the above Defense Plant Corporation well was drilled.

#### FOREIGN TRADE 10

The latest published information regarding United States exports and imports of potash salts in 1941 (chapter of Minerals Yearbook, 1941) covered only the period from January to September. In this chapter, figures for the full year 1941 as well as for the year 1942 are given.

39 pp., 6 figs.

16 Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

<sup>\*</sup> Gabriel, Alton, and Dasher, John, Beneficiation of Alunite: Bureau of Mines Rept. of Investigations 3610, 1942, 20 pp.

\* Bureau of Mines, Thompson Magnesium Well, Grand County, Utah: War Minerals Report 12, 1942,

Imports.—The United States, formerly a large potash-importing nation, now imports only a few thousand tons of potash salts annually under World War conditions. In 1941—the first year in which domestic production of potash exceeded national demand—imports had fallen to 62,255 short tons. In 1942 they dropped to 21,328 tons.

Late in February 1943 the Alien Property Custodian announced the vesting in him (Vesting Order 929, February 22, 1943) of all outstanding capital stock of the German-owned Pioneer Potash Co. This company had been incorporated in the United States to import and sell potash of German origin following the dissolution and liquidation of the N. V. Potash Export My., Inc., at the outbreak of war between France and Germany. The stock of the Pioneer Potash Co. was registered in the name of and was owned by N. V. tot Financiering van Industrieele Ondernemeingen Finindo, a corporation organized under the laws of the Netherlands, all of whose issued and outstanding capital stock is owned by Verrekeningskantoor ("Leata"), a Netherlands corporation of Amsterdam, Holland. All the issued and outstanding capital stock of this company is owned by the Deutsches Kalisyndicat G. b. m. H. (German potash trust).

Details as to the quantity, average grade, and declared value of the various potash salts imported into the United States in 1941 and 1942, and the approximate K<sub>2</sub>O equivalent of the imports, are shown in the following tables.

Potash materials imported for consumption in the United States, 1941-42

			<u> </u>						
			1	941			19	42	
Material	Ap- proxi- mate equiv- alent as potash	Short	Approx equiv as po (K <sub>2</sub>	alent tash	Value	Short	Approx equiv as po (K <sub>2</sub>	alent tash	Value
	(K <sub>2</sub> O) (per- cent)	tons	Short tons	Percent of total	Value	tons	Short tons	Per- cent of total	value
Used chiefly in fertilizers:									
Muriate (chloride) Potassium-sodium ni-	56.4	14,671	8, 274	52.3	\$296, 367	1, 564	882	20.2	\$40, 195
trate mixtures, crude_	14.0	34, 541	4, 836	30.6	725, 846	14, 272	1,998	45.9	377, 703
Other potash fertilizer material 1	60.0	125	75	.5	1, 714	59	35	.8	889
Total fertilizer		49, 337	13, 185	83.4	1, 023, 927	15, 895	2,915	66. 9	418, 787
Used chiefly in chemical									
industries: Bicarbonate Bitartrate:	46.0			h	(	1,309	602	1	52,794
Argols Cream of tartar	20. 0 25. 0	12, 680 22	2, 536 6		4, 606, 751 14, 427	4, 051 (2)	810 (2)		1, 701, 901 1
Caustic	61. 0 80. 0	5 12	3 10	'	1, 235 4, 284	(2)	(2)		1
Chlorate and perchlo- rate	36.0	139	50	16.6	46, 232	35	- 13	33. 1	8, 733
siate)	42.0 28.0	(2) (2) (2)	(2) (2) (2)		360 14	(2)	(2)		158
Nitrate, refined Permanganate All other	46. 0 29. 0 50. 0	(2) 13 47	(2) 4 24		130 4, 352 25, 186	(2) 38	(2) <u>1</u> 9		21, 085
Total chemical		12, 918	2, 633	16.6	4, 702, 971	5, 433	1, 444	33. 1	1, 784, 674
Grand total		62, 255	15, 818	100.0	5, 726, 898	21, 328	4, 359	100.0	2, 203, 461

<sup>&</sup>lt;sup>1</sup> Chiefly wood ashes from Canada.

<sup>2</sup> Less than 1 ton.

Potash materials imported for consumption in the United States, 1941-42, by countries, in short tons

[Figures in parentheses in column headings indicate, in percent, approximate equivalent as potash (K<sub>2</sub>O)]

		Bita	rtrate			Potas-			7	otal
Country	Muri- ate (chlo- ride) (56.4)	Argols or wine lees	Cream of tartar	Caus- tic (80)	Car- bonate (61)	sodium nitrate mix- tures,	Chlorate and per- chlorate (36)	All other 1	Short	Value
		(20)	(25)			crude (14)				
1941						,				7 3 3 4 3
Algeria	1	816			l			1	816	\$329, 200
AlgeriaArgentina		3,747		1	l		l		3, 747	1, 154, 142
Brazil		136		l	1	1			136	56, 264
Brazil Canada Chile	16	15	1	1		ſ	9		158	11, 563
Chile	1	341	1 17		ł	34 541	1 14		34, 913	845, 011
China France					3			5	8	2, 183
France					1		31		31	2, 103
Germany							2			
Hong Kong							4		2	704
Innon								l	2	503
Morios							02	13	75	38, 001
MICKICO		35							35	336
Miorocco	l-=-===-	815							815	400, 877
Japan Mexico Moroceo Palestine	1,000								1,000	28,058
										3, 226
Portugal Spain		3, 264				l <b>.</b>			3, 264	1, 463, 069
Spain	13,655	3, 493	5				l		17, 153	1, 357, 011
DWedell	l			1 12	1	1	1 K		18	5, 123
owitzeriand	1		1				22		22	4, 887
United Kingdom	l							42	42	23, 870
										20,010
10/19	14, 671	12, 680	22	. 12	5	34, 541	139	185	62, 255	5, 726, 898
1942 Algeria		1 400							1 400	000 510
Argentina		1,403							1,403	830, 716
Drogil		1,042							1,042	195, 521
Brazil Canada Chile		247							247	156, 435
Canada	7	29	(2)	(2)			2	63	101	18, 463
Chile		242				14, 272		(2)	14, 514	437, 475
Mexico								l	22	1, 471
Morocco (French)		626							626	224, 382
Netherlands								1	1	335
Peru									3	1, 491
Portugal		940				1		1	249	119, 701
Spain		188	l						188	96, 561
Spain Switzerland U. S. S. R United Kingdom 3							• 33		33	7, 722
U. S. S. R.	1, 557		1				30		1, 557	39, 816
United Kingdom 3	,							1,342	1, 342	73, 372
								1, 072	1, 074	10,012
	1, 564	4, 051	(2)	(2)		14, 272	35	1,406	21, 328	2, 203, 461
	i	1	1	1				l		

Approximate equivalent as potash (K<sub>2</sub>O)—1941: 55 percent; 1942: 47 percent.

Exports.—Substantial quantities of potash-bearing materials were exported from the United States even in former years when this country was a large importer of potash. Japan was the principal buyer in 1939 but was exceeded by Canada in 1940 and 1941. In 1942, 81 percent of the total exports of potash-bearing materials went to Canada.

Reinstated in this chapter is a table of exports by countries, omitted

from the 1941 chapter for reasons of censorship.

Details regarding the exports of certain potassium-bearing fertilizer materials, by countries and by four subclasses, became available in the latter half of 1941. Such figures for 1942 are shown in a succeeding table.

Less than 1 ton.
 United Kingdom of Great Britain and Northern Ireland.

## Potash materials exported from the United States, 1938-42

	Fe	rtilizer	CI	hemical		Fe	rtilizer	Ch	emical
Year	Short tons	Value	Short tons	Value	Year	Short	Value	Short tons	Value
1938 1939 1940	84, 137 136, 750 93, 060	\$2, 599, 772 4, 446, 853 3, 141, 170	2, 616 3, 579 14, 180	\$485, 672 807, 987 3, 096, 909	1941 1942	91, 950 84, 402	\$2, 592, 697 2, 184, 044	12, 883 13, 306	\$2,972,137 3,611,294

# Potash materials exported from the United States in 1942, by countries, in short tons

			Fertilizers		
Country	Chloride	Sulfate	Potassic ferti- lizer materials <sup>1</sup>	Other	Total
Argentina	(2) 268	(²) 28		1 15	269 28 15
Barbados	1, 331 (2) 32, 795	1 5, 475	15, 478	224 22, 414	1, 331 225 76, 162
Colombia Cuba Mexico Mozambique	1, 942 46 45	544 1,396 25	1,859	114 106	544 5, 311 177 45
Panama Union of South Africa U. S. S. R Other countries	23	157		100	100 23 157 15
Total: Short tons Value	36, 456 \$1, 189, 979	7, 633 \$349, 468	17, 337 \$344, 683	22, 976 \$299, 914	84, 402 \$2, 184, 044

				Chem	nicals			
Country	Potas- sium iodides	Bichro- mate and chromate	Hy- droxide (caustic potash)	Acetate and mix- tures	Bicar- bonate and mix- tures	Carbon- ate and mixtures	Bitar- trate and mix- tures	Chlorate and mix- tures
Argentina Australia Brazil Canada Chile Colombia Cuba Egypt India Mexico Netherlands Indies New Zealand Union of South Africa U. S. S. R. United Kingdom 4 Uruguay Venezuela Other countries	4 11 14 2 (2) 8 5 (2) 3 9 (2) (3) (4) 	253 50 137 208 55 17 1 111 64 190 43 22 63	408 650 102 1,305 35 7 83 121 247 (2) 18 34 42 129 40 19 211	1	(2) 1 (2) 10 (2) (2) (2) (2) (2) 1 1	147 662 15 207 25 26 1 8 (2) 78 9 3 4	21 1 47 4 3 2 3 1 (2) (2) (2) (2) (2) (2) (3)	4 114 59 1 11 55 82 76 499 423 1 71 (2)
Total: Short tons Value	76 \$222,362	1, 292 \$317, 799	3, 454 \$546, 202	\$1,644	18 \$7, 343	2, 170	\$120, 884	1, 487 \$920, 405

See footnotes at end of table.

# Potash materials exported from the United States in 1942, by countries, in short tons—Continued

				Chemicals-	-Continue	eđ		
Country	Chromi- um sul- fate (chrome alum)	Cyanide and mix- tures	Nitrate and mix- tures	Perchlo- rate and mixtures	Permanganate and mixtures	Rochelle	Other	Total
Argentina Australia Brazil Canada Chile Colombia Cuba Egypt India 3 Mexico Netherlands Indies New Zealand	6 2 2 4 10 6 2 1	19 1 22 4 2 (2) (2) (2) (2) (2) 11 8	110 2 880 987 (2) 82 10 (2) (2) 206	(2)	1 6 6 63 2 1 2	1 2 50 1 2 8 2 	56 9 38 433 94 4. 20 2 32 40	1, 030 1, 498 1, 278 3, 321 235 208 142 285 733 1, 218
Union of South Africa. U. S. S. R. United Kingdom 4. Uruguay Venezuela Other countries.	(2) (2) 7 (2) 10	(²) (²) 2 2	(2) 959 (2) 7 55 111		(2) 1 16	25 (2) 2 2	1 47 111 9 4 5 59	154 1, 113 1, 095 101 106 618
Total: Short tons Value	\$16, 767	71 \$42,454	3, 409 \$511, 892	(2) \$567	\$64,820	\$96, 138	965 \$428, 128	13, 306 \$3, 611, 294

<sup>&</sup>lt;sup>1</sup> Containing 27 percent or more potassium oxide ( $K_2O$ ) equivalent, n. e. s., (25 percent  $K_2O$  content equivalent basis).

<sup>2</sup> Less than 1 ton.

<sup>3</sup> India and Dependencies (British India).

<sup>4</sup> United Kingdom of Great Britain and Northern Ireland.

#### Potash materials exported from the United States, 1941-42, by countries

		Fert	ilizers			Cher	nicals	
Country	1	941	1	942	19	H1	1942	
	Short tons	Value	Short tons	Value	Short tons	Value .	Short tons	Value
ArgentinaAustralia	172	\$10, 292	269 28	(1)	815 1, 198	\$183, 724 194, 354	1, 030 1, 498	(1)
Barbados Brazil Canada	3, 970 2, 693 48, 721	151, 695 115, 038 1, 203, 628	1,331 225 76,162	(1)	909 3, 688	271, 434 517, 350	(2) 1, 278 3, 321	(1)
ChileColombiaCuba	2 4,047	136	544 5,311	eeeeeee	220 230 87	77, 515 96, 761 45, 621	235 208 142	
Egypt ndia 3 apan	150 25, 075	10, 410 673, 028	(4)		443 474 1	102, 877 160, 969 250	285 733	(3)
MexicoVetherlands Indies Vew Zealand	73 821 1, 458	2, 998 31, 176 75, 749	177 (2)	(1)	588 261 60	169, 651 108, 119 19, 532	1, 218 55 116	(1)
Philippine Islands Union of South Africa U. S. S. R.	1,806 790	64, 395 39, 946	23 157	(1)	166 <b>433</b>	84, 537 114, 610	154 1, 113	(2)
Inited Kingdom 4 Iruguay enezuela	594 3 10	23, 961 227 669	2	<u>(i)</u>	1, 810 42 61	319, 406 11, 273 20, 381	1, 095 101 106	9998
ther countries	1, 565 91, 950	64, 040 2, 592, 697	172 84, 402	(¹) \$2, 184, 044	1, 397	473, 773 2, 972, 137	618	(1) \$3,611,2

Data not yet compiled on annual basis.
 Less than 1 ton.
 India and Dependencies (British India).
 United Kingdom of Great Britain and Northern Ireland.

#### WORLD PRODUCTION

Little information is available regarding the production of potash in foreign countries during recent years—for 1942, only figures for the United States, and for 1941, only those for the United States and Palestine. Since publication of the world-production table in Minerals Yearbook, 1941, a few additional figures for earlier years have become available; they are shown in the accompanying table. Four nations dominate the world potash industry—Germany,

Four nations dominate the world potash industry—Germany, United States, Soviet Russia, and Spain. Germany, now as heretofore, the dominant producer of western Europe as well as of the world, has bettered its position by the acquisition of the French and Polish potash industries and now holds all the important potash deposits of the western part of Europe except those of Spain. Soviet Russia, with its large reserves in the Solikamsk region, controls the potash industry of eastern Europe. In the Western Hemisphere the United States is by far the largest and almost the only potash producer. Its annual production, in terms of equivalent potash (K<sub>2</sub>O), in 1942 exceeded the latest known K<sub>2</sub>O output (1938) of France, at that time probably the second-largest producer in the world. The United States probably was the second-largest world producer in 1942; however, the relative position of the U. S. S. R. cannot be determined as statistics of its production are not available.


# World production of potash minerals and equivalent K<sub>2</sub>O, 1938-42, by countries, in metric tons<sup>1</sup>

[Compiled by B. B. Waldbauer]

	19	38	19	1939		1940		941	19	942
Country and mineral <sup>1</sup>	Output	Equivalent K <sub>2</sub> O	Output	Equivalent K <sub>2</sub> O	Output	Equivalent K <sub>2</sub> O	Output	Equivalent K <sub>2</sub> O	Output	Equivalent K <sub>2</sub> O
North America: United States, potassium salts South America: Chile, crude potassium nitrate	485, 291 (²)	287, 532 (²)	496, 007 (²)	283, 223 (²)	597, 150 62, 208	344, 437 8, 585	894, 895 (²)	476, 156 (²)	1, 149, 810 (²)	616, 162 (²)
Europe: France (Alsace), crude potassium saltsGermany, crude potassium salts:	3, 374, 811	581, 790	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)
Carnallite   Kainite, sylvinite, and hartsalz  Italy, alunite	1, 874, 375 14, 567, 896 2, 778	} 1, 861, 000 333	(2) (2)	(2) (2)	(2) (2)	(2) (2)	(2) (2)	(2) (2)	(2) (2)	(2) (2)
Poland, crude potassium salts:  Kaintte	120, 100 427, 200 19, 644 4 49, 572	12, 010 93, 984 2, 358 (2)	(2) (2) (2) (2) 143, 393	(2) (2) (2) (2) (2)	(2) (2) (2) (2) 291, 373	(2) (2) (2) (2) (2)	(2) (2) (2) (2)	(2) (2) (2) (2) (2)	(2) (2) (2) (2) (2)	(2) (2) (2) (2) (2)
U. S. S. R., crude potassium salts  Asia: China, potash Chosen, alumite India (British), nitrate of potash Palestine, crude potassium salts 7.	(2) 6 14 (2) 6 8, 200	\$ 122,000 (2) (2) \$ 4,000	(2) 6 4 (2) 8, 697	(2) (2) (2) 4, 175 31, 764	(2) 3, 317 (2) (2) (2) (2)	(2) (2) (2) (2) (2)	(2) (2) (2) (2) (2)	(2) (2) (2) (2) (2)	(2) (2) (2) (2) (2)	(2) (2) (2) (2) (2)
Palestine, crude potassium salts 7Africa: Eritrea, niccoli salts 9Australia, alunite	58, 118 (2) 445	29, 059 (2) (2)	8 63, 527 (2) (2)	31, 764 (2) (2)	88, 961 (2) (2)	(2)	101, 681 (2) (2)	(2)	(2) (2) (2)	(2)

In addition to countries listed Iran is reported to produce a small quantity of potash salts, but statistics of production are not available.

Data not available.
Includes some natural kieserite.
Salable.
Salable.
Estimated production (Imperial Institute, London).
Exports of potassium carbonate.
Exports of potassium earbonate.
Exports.
Extracted from waters of Dead Sea.
Exports.
Extracted from waters of Red Sea.



### **MICA**

#### By G. RICHARDS GWINN and K. G. WARNER

#### SUMMARY OUTLINE

	Page	Programme and the second secon	Pag
Summary	1463	Built-up mica.	147
Salient statistics	1464	Possible substitutes	147
Domestic production	1464	Prices	147
Sheet mica	1464	Foreign trade	147
Scrap mica	1465	Imports	147
Ground mica	1465	Evnorte	- 147
Total consumption of block and sheet mica	1467	World production	147
Mica splittings	1468		740

#### SUMMARY

Production of all kinds of mica except splittings increased in 1942. Although the over-all increase of sheet and punch (4 percent over 1941) was not as great as expected in view of the intense stimulation exercised to supply growing war needs, the quantity of the better grades increased substantially.

In June 1942, the Colonial Mica Corporation, a nonprofit organization, was designated by the Metals Reserve Co. as its agent to purchase strategic mica for the war industries, and in December 1942 this corporation was designated as the sole buyer of domestic strategic

mica.

Splittings, which are used in a great variety of built-up mica products, are imported chiefly from India, although small quantities have been split mechanically in the United States, and an increasing quantity has been imported from Mexico. The Mexican splittings consist chiefly of Indian block mica re-exported to Mexico, where cheap labor is available for the manufacturing process.

The accompanying table of salient statistics gives the outstanding

features of the mica industry during the past 5 years.

Approximately 65 percent of the total quantity of good-stained and better grades, sizes 5, 5%, and 6, are used for military radio condensers and magnetos, and up to the present time it has not been shown that

lower than good-stained can be used in these products.

Stocks of good-stained and better mica on hand December 31, 1942, were sufficient for 8½ months at the average rate of consumption during 1942. A break-down by sizes and qualities, however, shows that although the supply of grades poorer than good-stained is ample, the supply of good-stained and better grade of sizes 5, 5½, and 6 is not keeping pace with consumption. However, in the event of a critical situation it would be possible, though uneconomical, to use the larger sizes instead of the smaller to relieve the shortage.

THE PARTY OF THE P

Salient statistics of the mica industry in the United States, 1938-42

	1938	1939	1940	1941	1942
Domestic mica sold or used by producers:					
Total uncut sheet and punch:		100			
Pounds	939, 507	813, 708	1, 625, 437	2, 666, 453	2, 761, 844
Value	\$139, 333	\$138, 963	\$291,685	\$566, 858	\$725,030
Average per pound	\$0.15	\$0.17	\$0.18	\$0.21	\$0. 26
Company 1				7	40.20
Short tons	20, 257	24,672	22, 386	32, 500	43, 262
Value	\$256, 382	\$311, 895	\$314, 565	\$442, 789	\$671, 165
Average per ton	\$12.66	\$12.64	\$14.05	\$13.62	\$15.51
Total sheet and scrap:1					
Short tons	20, 727	25, 079	23, 199	33, 833	44, 643
Value Total ground: <sup>1</sup> Short tons	\$395, 715	\$450, 858	\$606, 250	\$1,009,647	\$1,396,195
Total ground: 1	•		*****	13, 111, 111	4-,000,-00
Short tons	27, 086	30, 924	27, 984	43, 419	46, 979
Value	\$924, 554	\$1, 156, 333	\$1, 016, 628	\$1, 532, 351	\$1,653,358
Value Consumption of splittings: 2				. , . ,	, , , ,
Pounds	1,667,806	3, 423, 044	4. 918. 861	7, 297, 628	6, 636, 639
Pounds Value	\$612, 465	\$1,089,683	\$1, 725, 522	\$2,832,939	\$2, 835, 421
Imports for consumption:					
Total uncut sheet and punch:					
Pounds	391, 125	902, 598	1, 534, 188	2,016,852	3, 244, 857
Value	\$113, 403	\$271,072	\$576, 565	\$1, 119, 584	\$2, 136, 797
Scrap:					
Short tons	4, 450	4, 279	3,061	1, 251	2, 179
Value	\$28, 590	\$29, 493	\$22, 611	\$12, 791	\$25, 879
Total sheet and scrap:					
Short tons	4,646	4, 730	3,828	2, 259	3,801
Value	\$141,993	\$300, 565	\$599, 176	\$1, 132, 375	\$2, 162, 676
Manufactured:					
Short tons	1, 115	1, 550	3,860	6,041	7, 479
Value	\$522, 426	\$758, 745	\$1, 884, 952	\$3, 282, 656	\$6, 882, 199
Total imports:					
Short tons	5, 761	6, 280	7,688	8,300	11, 280
Value	\$664,419	\$1,059,310	\$2, 484, 128	\$4, 415, 031	\$9, 044, 875
Exports (all classes of mica):					
Short tons	1,772	1,827	903	1, 163	1,001
Value	\$183, 889	\$226, 364	\$191,550	\$280,810	\$303, 526

Includes mica recovered from kaolin and mica schists, as follows: 1938, 6,550 tons, \$86,602; 1939, 10,011 tons, \$108,899; 1940, 9,674 tons, \$138,148; 1941, 15,583 tons, \$185,486; 1942, 20,481 tons, \$315,807.
 Exclusive of a nominal quantity of splittings produced in the United States and South America.

#### DOMESTIC PRODUCTION

Sheet mica.—Production in the United States increased to 2,761,844 pounds in 1942, valued at \$725,030, compared with 2,666,453 pounds, valued at \$566,858 in 1941. Eighty-eight percent of this, or 2,425,645 pounds, valued at \$282,900, consisted of punch mica.

North Carolina, the largest producer in the United States, supplied 60 percent of the total punch and 61 percent of the larger sheet in 1942, compared with 61 and 54 percent, respectively, in 1941; and although this represents an advance in production, it failed to meet expectations.

South Dakota, which produced a large quantity of sheet and punch mica in 1941, increased its output in 1942 and became the second-largest producing State with an output of 399,224 pounds, valued at \$75,687. Production in both Connecticut and New Hampshire declined in 1942.

The change in preparation from half-trim to three-quarter or full-trim of a large part of the mica produced had an important bearing on the increase in output. Because of better preparation, the yield per pound to the consumer was higher in 1942 than in any previous year. The increase in amount of usable mica per pound received was large enough so that although the quantity produced in New Hamp-

shire and Connecticut decreased, the value of the material was greater than in any previous year.

Mica sold or used by producers in the United States, 1930-42

			Sheet	mica			Scrat	mica		
Year	Uncut punch and circle mica <sup>1</sup>		Uncut mica larger than punch and circle		Total uncut sheet mica		and mica recovered from kaolin and schists		Total	
	Pounds	Value	Pounds	Value	Pounds	Value	Short tons	Value	Short tons	Value
1930-34 (average)	589, 668 888, 313 1, 312, 900 774, 121 665, 755 1, 405, 305	\$25, 764 46, 408 70, 493 45, 566 39, 207 116, 087	381, 638 165, 386	214, 751 93, 767 99, 756	1, 140, 724 1, 694, 538 939, 507	\$95, 694 185, 714 285, 244 139, 333 138, 963 291, 685	10, 869 21, 986 25, 196 20, 257 24, 672 22, 386	354, 737 256, 382 311, 895	11, 241 22, 557 26, 043 20, 727 25, 079 23, 199	\$240, 791 471, 226 639, 981 395, 715 450, 858 606, 250
1941: Connecticut New Hampshire. North Carolina. South Dakota Other States 2	157, 816 368, 794 1, 440, 349 285, 888 89, 390	11, 135 36, 172 124, 355 28, 589 6, 696	26, 113 174, 514 12, 805	9,336	1, 614, 863 298, 693	129, 896 65, 104 318, 783 37, 925 15, 150	171 18, 234 1, 611 12, 283	3, 983 3, 700 268, 596 27, 616 138, 894	327 369 19, 041 1, 760 12, 336	133, 879 68, 804 587, 379 65, 541 154, 044
	2, 342, 237	206, 947	324, 216	359, 911	2, 666, 453	566, 858	32, 500	442, 789	33, 833	1, 009, 647
1942: Connecticut New Hampshire North Carolina South Dakota Other States 2	196, 377 290, 288 1, 451, 340 363, 909 123, 731	14, 231 26, 320 180, 904 39, 845 21, 600	35, 315	35, 842	342, 939 1, 654, 895 399, 224	30, 801 57, 995 505, 634 75, 687 54, 913	200 303 24, 145 2, 545 16, 069	7, 234 485, 560 44, 579	311 474 24, 972 2, 745 16, 141	35, 244 65, 229 991, 194 120, 266 184, 262
	2, 425, 645	282, 900	336, 199	442, 130	2, 761, 844	725, 030	43, 262	671, 165	44, 643	1, 396, 195

Includes small quantities of splittings in certain years.
 1941: Alabama, Arizona, California, Colorado, Georgia, Maine, New Mexico, New York, Pennsylvania,
 South Carolina, Vermont, Virginia, and Wyoming. 1942: Alabama, California, Colorado, Georgia, Idaho,
 Maine, Massachusetts, New Mexico, South Carolina, Texas, Vermont, and Virginia.

Scrap mica.—Production of scrap mica increased to 43,262 short tons valued at \$671,165, compared with 32,500 tons valued at \$442,789 in 1941. Besides mine scrap, this tonnage included mica recovered from washing kaolin or kyanite or by milling schist, which amounted to 20,481 short tons valued at \$315,807, compared with 15,583 tons valued at \$185,486 in 1941.

Ground mica.—Production of ground mica in 1942 reached 46,979 short tons valued at \$1,653,358, compared with 43,419 tons valued at

\$1,532,351 in 1941.

Production of wet-ground mica decreased. Most of this is used in war materials, such as paints, protective coatings on tents and

tarpaulins, plastics, and welding rods.

Dry-ground mica, which constitutes about 77 percent of all ground mica, is used chiefly in the roofing trade as a backing for rolled asphalt roofing and shingles to prevent sticking and, often, as a decorative surfacing for these materials. A small proportion of the finely ground material may be incorporated into the body of the roofing itself. Ground phlogopite mica is used as an ingredient in certain types of molded electrical insulation, in which it is bonded with natural or synthetic resins, gums, asphalts, rubber, silicate cements, or lead borate.

The history of the scrap- and ground-mica industries over a series of years is indicated in figure 1.




FIGURE 1.—Scrap and ground mica sold in the United States, 1923-42.

# Ground mica sold by producers in the United States, 1938-42, by methods of grinding

Year	Dry-gr	ound 1	Wet-g	round	Total 1		
1938 1939	Short tons  19,757 23,222 21,809	Value \$466, 959 547, 539 515, 930	7, 329 7, 702 6, 175	Value \$457, 595 608, 794 500, 698	27, 086 30, 924 27, 984	\$924, 554 1, 156, 333 1, 016, 628	
1941 1942	- 31, 914 - 36, 369	733, 559 805, 163	1 11, 505 10, 610	1 798, 792 848, 195	43, 419 46, 979	1, 532, 351 1, 653, 358	

<sup>&</sup>lt;sup>1</sup> Includes mica from kaolin and schists; some from sericite schist included in wet-ground in 1941.

# Ground mica sold by producers in the United States to various industries, 1941-42

		1941		1942			
Industry	Qua	ntity		Qua			
*	Short tons	Percent of total	Value	Short tons	Percent of total	Value	
Roofing 1	25, 178 3, 219 3, 476 4, 020 7, 526	58 8 8 9 17	\$498, 946 256, 067 223, 182 253, 294 300, 862	28, 342 2, 168 1, 754 6, 819 7, 896	60 5 4 14 17	\$561, 205 168, 178 115, 563 418, 548 389, 864	
	43, 419	100	1, 532, 351	46, 979	100	1, 653, 358	

Includes mica from kaolin and schist.
 Includes mica used for molded electric insulation, house insulation, Christmas-tree snow, manufacture of axle greases and oil, annealing, pipe-line enamel, plastic specialties, textiles, and other purposes.

MICA 1467

Control of the second s

THE THE PARTY OF T

## TOTAL CONSUMPTION OF BLOCK AND SHEET MICA

Government stimulation of domestic production and imports began to function efficiently in 1942. Monthly statistics of consumption and stocks of specific grades of block mica were first collected by the Bureau of Mines for July 1940.

Almost all strategic mica is consumed in the production of aircraft and tank magnetos, spark plugs, military radios, and sound-detection

equipment.

Urgently needed strategic grades of Indian mica have been im-




FIGURE 2.—Block and sheet mica (cut) and splittings imported for consumption in the United States, and sales of domestic sheet and punch mica, 1924-42.

ported by air since September 1942. Conservation orders and shortages of materials for commodities that were manufactured chiefly for civilian consumption curtailed the demand for splittings and enabled industry and the Government to accumulate adequate stock piles of muscovite and phlogopite splittings.

In 1942, as in 1941, condenser mica was in greatest demand; and as demand outgrew production and import of the better grades, the quality of the mica allocated for this use was lowered to include

good-stained material.

Figure 2 summarizes graphically the situation with respect to imports and domestic production. As reported by the Mica-Graphite

Division of the War Production Board, good-stained and better comprise about 60 percent of all imports, and sizes 5, 5½, and 6 of both imported and domestic material are in greatest demand. Stocks of good-stained and better at the end of the year were sufficient for 8½ months at the average rate of consumption in 1942, although stocks of specific size groups ranged from 11 to only 2.8 months' supply. Domestic production furnished approximately one-tenth of the total new supply for the year of good-stained and better and one-eighth of all qualities. However, with the improvement in trimming, as well as increase in production, it is expected that the percentage of the total supply furnished by domestic production will increase.

### MICA SPLITTINGS

Consumption of splittings fell below the record high of 1941, and Government stocks increased from 4,928,000 pounds on January 1, 1942, to 11,374,000 pounds by the end of the year. Industrial stocks remained relatively constant although slightly below the 1941 level. The decline in total consumption of splittings, which began in the third quarter of 1941, continued through the first quarter of 1942. However, beginning with the second quarter of 1942 and throughout the rest of the year the consumption of splittings, muscovite and amber combined, increased. Consumption of amber splittings alone reached a peak in the second quarter of the year and then declined gradually throughout the rest of the year, whereas the consumption of muscovite splittings increased in each quarter.

Grade 6 loose splittings, which are produced in three qualities—first, second, and third—constituted 81 percent of the total consumption of muscovite splittings during the fourth quarter of 1942. In the corresponding quarter of 1941 this size made up 80 percent of the total. Nearly equal amounts of first- and third-quality splittings were consumed, but consumption of No. 2 quality was greater than that of Nos. 1 and 3.

Consumption and stocks of mica splittings in the United States, 1938-42, by sources, as reported by the consumers

Year	In	dia	Car	ada	Mada	gascar	Total	
	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value
Consumption: 1								
1938	1, 446, 349	\$511,674	41, 100	\$20, 401	180, 357	\$80, 390	1, 667, 806	\$612, 46
1939	2, 995, 626	905, 763	107, 101	44,065	320, 317	139, 855	3, 423, 044	1, 089, 68
1940	4, 252, 120	1, 358, 534	54, 044	28, 491	612, 697	338, 497	4, 918, 861	1, 725, 52
1941	6, 473, 459	2, 334, 432	179, 783	131,350	644, 386	367, 157	7, 297, 628	2, 832, 93
Stocks in con-	5, 998, 614	2, 415, 709	117, 295	79, 752	520, 730	<b>3</b> 39, 960	6, 636, 639	2, 835, 42
Stocks in con- sumers' hands	:	-						
Dec. 31:								l
1938	4, 057, 681	1, 128, 075	55, 827	24,378	631.119	273, 926	4, 744, 627	1 400 27
1939	2, 754, 748	857, 656	52, 523	17. 697	673, 354	273, 465	3, 480, 625	1, 426, 37 1, 148, 81
1940	4, 620, 934	1, 776, 974	53, 378	35, 581	738, 489	410, 068	5, 412, 801	2, 222, 62
1941	9, 212, 891	3, 434, 336	115, 529	81, 988	223, 235	134, 143	9, 551, 655	3, 650, 46
1942	8, 202, 240	3, 367, 788	257, 591	178, 082	321, 529	201, 274	8, 781, 360	3, 747, 14

<sup>&</sup>lt;sup>1</sup> Exclusive of a nominal quantity of splittings produced in the United States and South America.

Before 1942, production of splittings in the Western Hemisphere was confined largely to phlogopite splittings produced by hand in Canada and small quantities of phlogopite imported from Canada and

1469

split mechanically in the United States. However, in 1942 splittings were produced in Mexico from block mica, most of which originated in India and Brazil.

The table of imports for consumption in 1942 includes 6,720 pounds of splittings imported from Japan. This is part of a shipment received in the foreign-trade zone at Staten Island in 1940




FIGURE 3.—Consumption of specified sizes and qualities of mica splittings in the United States, by quarters, July 1941 to December 1942.

and remained there. The 6,720 pounds represent that portion of

the shipment released to the industry in March 1942.

The new 1942 supply was more than enough to meet requirements for the year. Stocks held at the end of 1942 by the Government and industry were adequate for about 3 years at the 1942 rate of domestic consumption. Consumption of splittings from July 1941 through December 1942 is summarized graphically, on a quarterly basis, in figure 3.

## BUILT-UP MICA

Curtailment in the manufacture of electrical appliances and other consumers' durable goods, together with restrictions imposed on mica through conservation orders, caused the demand for built-up products to decline in the latter half of 1941 and the first quarter of 1942. However, as production of military equipment increased, demand for this material rose, particularly for making certain electric-generator and motor parts in which it is the standard irreplaceable insulating material. Consumption of built-up mica, therefore, began to increase after the first quarter and continued to do so during the remainder of the year.

Built-up mica produced in the United States, 1941-42, by kinds of product 1

Product	194	11	1942		
	Pounds	Value	Pounds	Value	
Molding plate Segment plate Heater plate Flexible (cold) All other (tape, etc.)	1, 874, 000 2, 317, 000 539, 000 706, 000 1, 199, 000	\$1, 854, 000 2, 599, 000 789, 000 754, 000 2, 089, 000	1, 599, 000 2, 045, 000 212, 000 649, 000 1, 628, 000	\$1, 552, 000 2, 367, 000 303, 000 743, 000 2, 794, 000	
	6, 635, 000	8, 085, 000	6, 133, 000	7, 759, 000	

<sup>1</sup> Partly estimated.

# POSSIBLE SUBSTITUTES

Every effort is being made to conserve our supplies of high-grade sheet mica by stipulating use of the smallest possible sizes, by requiring use of lower qualities wherever possible, by minimizing spoilage and

wastage, and by finding substitutes.

Under rules established by the American Institute of Electrical Engineers, mica is not required in class "A" insulation but has been used to a considerable extent because of a greater margin of safety with particular reference to heat and fire resistance. In induction motors, varnished cloth has been substituted for mica, and a clothbase, phenolic, laminated compound has been substituted as insulation between the decks of strip-wound commutating field coils. Such substitutes may serve in particular applications as indicated, but a substitute for the high-grade mica now required in certain types of military equipment has not been found. Several promising new materials are in process of development, and although each has characteristics similar to those of mica, none possesses the particular combination of characteristics enjoyed by mica. The War Production Board estimates that substitutes, when and if they are fully developed and approved by the Armed Services, may replace 10 to 15 percent of the mica now required in certain fields. However, none of the substitutes for high-grade mica have yet passed the laboratory stage.

#### PRICES

Mica is marketed in a confusing variety of sizes (grades) and classes (qualities) ranging in value from a fraction of a cent a pound for small, stained, imperfect flakes or scrap to over \$20 a pound for exceptionally large, flat, clear, crystal sheets. Not only does marketable mica vary greatly in size, from small punch to 8 by 10 inches and larger, but for each grade there are at least nine different qualities, ranging from clear to black-stained.

MICA 1471

The state of the s

Prices for Indian mica were raised because of increasing cost of insurance and ocean transportation. Prices for domestic punch and circle mica were increased in an effort to stimulate domestic production. These two classes were chosen on the theory that since they represented the bulk-line product, an increase in the price of these classes would afford the maximum encouragement to miners. However, this was not satisfactory because the value of the other sizes increased and that of punch and circle mica remained stationary.

The Colonial Mica Corporation, agent for the Metals Reserve Co., then set up a schedule of prices they would pay miners for strategic grades of mica. Mica thus purchased was allocated to processors and manufacturers at the current market price. To get the maximum amount of strategic material, this corporation also bought non-strategic mica or assisted miners in marketing this low-grade material.

The price scale on which Colonial Mica purchased strategic mica was a base price only. Mica poorer than No. 1 grade was subject to a discount from this scale, the exact amount of which depended on the judgment of Colonial Mica Corporation buyers. The base price was

revised several times during the year.

It was hoped that production of nonstrategic grades of mica would increase with increase in strategic grades, but most miners brought in only the highest-price material, leaving the lower-grade sheet, punch, and scrap on the mine dumps. Therefore, on November 19, 1942, new maximum prices for nonstrategic punch and sheet mica were issued by the Office of Price Administration under Order No. 141, section 3 (b), of the General Maximum Price Regulation. They ranged from 12 cents a pound for punch to \$2 per pound for sheet mica 6 by 8 inches. This step failed to remedy matters, which became so acute by January 1943 that several mica grinders were forced to close their plants temporarily. A meeting of industrialists and representatives from the Office of Price Administration was called by the War Production Board, and the scale of prices for nonstrategic grades of mica was revised in an effort to relieve the fast-developing shortage. scale was released on March 20, 1943, by the Office of Price Adminis-Nonstrategic punch and sheet mica, scrap mica, and crude mica schist were removed from price control. The maximum price of . domestic ground mica, mica schist, water-washed mica, and micronized mica was raised \$5 per short ton.

Trade-journal quotations and average sales value of domestic uncut sheet mica per pound in 1942

	Trade-journa	l quotations 1	Average value 2		
Size	Dec. 18, 1941	Dec. 3, 1942	Clear	Stained or spotted	
Punch 11½ by 2 inches 2 by 2 inches 2 by 3 inches 3 by 3 inches 3 by 4 inches 3 by 4 inches 4 by 6 inches 6 by 8 inches 8 by 10 inches 8 by 10 inches	\$0. 10-\$0. 15 .4565 .6085 1. 301. 50 1. 902. 05 2. 152. 25 2. 602. 75 3. 603. 70 5. 256. 00 8. 509. 50	\$0. 15-\$0. 20 . 75- 1. 00 1. 50- 1. 75 2. 50- 2. 75 2. 75- 3. 50 3. 75- 4. 25 4. 75- 5. 00 5. 75- 6. 25 6. 50- 8. 00 9. 50-10. 50	\$0. 141 1. 044 1. 615 2. 445 2. 978 3. 575 4. 180 5. 205 7. 119 13. 466	\$0. 09 . 88 . 51 . 76 . 92 1. 19 1. 51 1. 68 2. 89 4. 75	

Engineering and Mining Journal (Metal and Mineral Markets) quotations for No. 1 or No. 2 quality,
 o. b. North Carolina; stained qualities take 25 to 35 percent discount.
 Calculated from reports of 1942 sales by domestic producers to the Bureau of Mines.

Recommended selling prices of domestic uncut sheet mica per pound by the Colonial Mica Corporation, 1942 <sup>1</sup>

[Prices per pound, packed, ex warehouses]

Size	Grade	No. 1				No. 3.(BS)		
	Grade	Full kt.	¾ kt.	½ kt.	Full kt.	¾ kt.	½ kt.	½ kt.
Punch1 by 1½ inches								\$0. 12
1 by 1½ inches 1½ by 2½ inches Circle 1½ by 2 inches	No. 6 No. 5½	\$0.80 1.80	\$0.65 1.45	\$0.80	\$0.55 .90	\$0.40 .70	\$0. 45	. 18
2 by 2 inches 2 by 3 inches	No. 5 No. 4	2.40 4.30	1.90 3.20	1.20 2.00 2.50	1. 50 2. 75	1.15 2.05	$\left\{\begin{array}{c} .90 \\ 1.50 \\ 1.85 \end{array}\right.$	. 25 . 45 . 60
3 by 3 inches 3 by 4 inches 3 by 5 inches	No. 3 No. 2	5. 00 5. 80	3.75 4.60	2.75 3.25 4.00	3. 15 4. 00	2. 50 3. 25	$\left\{\begin{array}{c} 2.00 \\ 2.50 \\ 3.00 \end{array}\right.$	.75 1.00 1.30
4 by 6 inches	No. 1 No. A-1 Special	7.50 9.00 12.00	6. 00 7. 50 9. 00	5. 50 7. 00	4.80 6.00 7.75	4.00 5.00 6.00	4. 10 5. 25	1. 60 2. 00

<sup>1</sup> Data from War Production Board, Mica-Graphite Division, Mica Release 5, November 14, 1942.

## FOREIGN TRADE 1

Imports.—In 1942, total imports of all kinds of mica increased to 11,280 short tons valued at \$9,044,875, compared with 8,300 tons valued at \$4,415,031 in 1941. This was spread over all grades of mica. Waste and scrap phlogopite imports nearly doubled, and those of untrimmed phlogopite increased 41 percent. The higher grades of sheet mica also increased substantially. Further details on imports, by kinds and sources of origin, may be found in the following tables.

Exports.—Exports of both unmanufactured and manufactured mica were lower in 1942 than 1941, owing to greater requirements of our war industries and the shortage of shipping space.

Mica imported for consumption in the United States in 1942, by kinds and by countries

					Unmar	ufactur	ed				
	Waste a more th	and scra nan 5 ce	p, value nts per p	ed not ound	phlog	mmed copite		. (	Other		
Country	Phiogopite (duty, 15 per- cent)		Other (duty, 25 per- cent)		which no rectangular piece exceed- ing in size 1 inch by 2 inches may be cut (duty, 10 percent)		Valued not above 15 cents per pound n. e. s. (duty, 4 cents per pound)		Valued above 15 cents per pound (duty, 4 cents per pound + 25 percent)		
	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value	
Africa: Madagascar_Argentina_Bolivia_Brazil_Canada_Chile_Guatemala_India and Dependen-	4, 357, 536	\$25, 879			232, 431	\$32, 799	242, 688 237, 221 72, 521 233		2, 910 966, 502 118, 302 516	212, 323 3, 245 627, 101 86, 629	
cies Mexico Peru United Kingdom 1							25, 982 4, 515 12, 157	3, 473 666 1, 222	5, 564	1, 804 1, 367	
Total: 1942 1941	4, 357, 536 2, 434, 080			\$339	232, 431 164, 870	32, 799 21, 904	595, 317 473, 749	70, 545 60, 363	2, 417, 109 1, 378, 233	2, 033, 453 1, 037, 317	

<sup>&</sup>lt;sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

<sup>&</sup>lt;sup>1</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

Mica imported for consumption in the United States in 1942, by kinds and by countries—Continued

			Manufact	ured—Fili	ns and s	plittings		
	Not cut	or stamp	ed to dim	ensions	C			
Country	Not above 12 ten- thousandths of an inch in thick- ness (duty, 25 percent)		Over 12 ten- thousandths of an inch in thick- ness (duty, 40 percent)		dime (duty,	ped to nsions 45 per- nt)	Total films and splittings	
	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value
Africa: Gold Coast			<i>e</i> :		11, 325	\$29, 445	11, 325	\$29,445
Madagascar Bolivia	651, 764		119	\$127		1, 015, 236	651, 764 119	192, 540 127
Brazil Canada Chile Guatemala			300 79	170	117	478	114, 991 79 228	966 206 154
India and Dependen- cies	10, 228, 470	2, 995, 872	1, 884, 105	1, 208, 737 2, 225	110, 236	286, 234	12, 222, 811 6, 720	16 777
Japan Mexico Nigeria United Kingdom 1	1		11,073 1,600	21, 391 50			132, 190 1, 600	92, 736 50
Total: 1942		3, 349, 170	1, 976, 125	1, 266, 878	511, 265	1, 331, 393 39, 272	13, 608, 973 11, 689, 467	5, 947, 441
				7	/Ianufactu	red—Othe	r	
Country	Country  Manufactured— Cut or stamped to dimensions, shape, or form (duty, 40 percent)		Mica pla built-u (duty, 40	p mica	of which the con materia value	ufactures n mica is nponent l of chief (duty, 40 cent)	Ground or pulverized (duty, 15 percent)	
	Pounds	Value	Pounds	Value	Pounds	Value	Pounds	Value
Brazil Canada Guatemala	39, 631 4, 355 621	\$99, 992 8, 797 494		\$514	285	\$556	934, 645	\$7,598
India and Dependen- cies	355, 834	809, 912	82 8, 604			898		
Total: 1942 1941						1, 454 7, 025	934, 645 197, 750	

<sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

# Mica and manufactures of mica exported from the United States in 1942, by countries

	Unmanufactured		Manufactured					
Country			Ground or p	oulverized	Other			
	Pounds	Value	Pounds	Value	Pounds	Value		
North America: Canada Cuba Mexico Other North America	400, 268	\$4, 270	737, 675 17, 148 15, 025 152	\$29; 064 861 913 23 -	99, 956 2, 973 28, 979 1, 724	\$184, 210 1, 199 9, 856 4, 879		
South America: Argentina. Brazil			31, 598 400	1, 233 21	837 5, 978 2, 881	3, 997 9, 417 5, 633		
Chile Venezuela Other South America Europe:			350, 000 6, 000	8, 997 282	750 Z32	299 1, 770		
U. S. S. R. United Kingdom 1			198, 360	6, 520	3, 416	6, 926		

<sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

Mica and manufactures of mica exported from the United States in 1942, by countries Continued

			Manufactured					
Country	Unmanui	actured	Ground or 1	oulverized	Other			
	Pounds	Value	Pounds	Value	Pounds	Value		
Asia:					2.000	40,000		
India and Dependencies Netherlands Indies Other Asia			40, 000 24, 200	\$900 1, 160	3, 006 1, 540 1, 030 12	\$9, 839 1, 827 1, 891 114		
Africa. Oceania.			24, 500	736	1, 376 2, 224	2, 877 3, 812		
Total: 1942	400, 268 432, 775	\$4, 270 5, 141	1, 445, 058 1, 759, 176	50, 710 56, 207	156, 914 134, 932	248, 546 219, 462		

### WORLD PRODUCTION

Aside from India, where the military situation and transport are the chief problems and their future status is unpredictable, our foreign supplies have come largely from Brazil. New sources are being developed, and particular efforts are being made to expedite production in India and Brazil. The Board of Economic Warfare has sent specialists and engineers to the other Americas in search of new deposits and to advise local producers on mining and preparation of mica for The following table shows world production by countries from 1937 to 1942 so far as statistics are available.

World production of mica, 1937-42, in metric tons 1 [Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
North America:			100			
Canada (sales)	857	470	969	819	1, 582	1, 857
Mexico (exports)	(2)	(2)	(2)	39	36	1,001
United States (sold or used by pro-		1 "		1	- 0	-
ducers) 3	23, 626	18, 803	22,751	21,046	30, 693	40, 499
South America:	1,11			. ,		20, 200
Argentina Bolivia (exports)	4 225	4 250	4 298	4 442	8 550	6 441
Bolivia (exports)	9	4.		1	3	13
Drazu (exports)	330	521	435	1, 117	867	866
Peru	5	24	9	4	8	10
Europe:			-			
Italy Norway (exports)		122	(2)	(2) (2) (2) (2)	(2) (2) (2) (2)	(2)
Rumania	42 27	104	25	(2)	(2)	(2) (2) (2) (2)
Sweden	68	22	18	(2)	(2)	(2)
Asia:	08	131	126	(2)	[ (2) ]	(2)
Ceylon (exports)	1	(7)	(7)		/ <sub>(0)</sub>	(0)
Chosen	5 70	(7)	(7)	(2)	(2) (2)	(2) (2)
India, British (exports)	15, 106	8,896	10, 104	8 7, 067		(2)
A frica :	10, 100	0,000	10, 104	* 1,001	8 11, 521	14, 398
Madagascar	583	677	(2)	531	479	(2)
Nigeria		3	(2) (2)		(3) 4/8	(2) (2) (2)
Portuguese East Africa			17	(2)	(2) (2)	\ <u>2</u> \
Rhodesia:				. ()		(-)
Northern	4	4	2	(2)	(2)	(2)
Southern	17	13	<u>-</u>	(2) (2)	(2) (2) (2)	(2) (2) (2)
Tanganyika Territory	71	37	36	` 10	25	24
Union of South Africa: Transvaal	1,740	1, 116	972	1, 252	920	ì í, 062
Oceania:	•	· 1		-,	• • •	1,002
Australia:						
Northern Territory	42	52	32	35	26	(2)
South Australia	43	17	. 56	70	(2)	(2)
Western Australia			(7)	1	(2) (2) (2)	(2) (2) (3) (2)
New Zealand	(2)	(2)	1		(2)	(2)

<sup>&</sup>lt;sup>1</sup> In addition to the countries listed, mica is also produced in Australia (Queensland and New South Wales), Eritrea, Kenya, and U. S. S. R., but data on production are not available.

<sup>2</sup> Data not available.

Includes following quantities recovered from kaolin and schists: 1937, 9,558 tons; 1938, 5,942 tons; 1939, 9,082 tons; 1940, 8,776 tons; 1941, 14,137 tons; 1942, 18,580 tons.
 Rail and river shipments.
 Official estimate.
 Fiscal year ended March 31 of year following year stated.
 Exports.
 Less than 1 ton.
 January to October, inclusive.

1475 MICA

The second secon

Argentina.—All of the mica produced is muscovite and is classified as 80 percent stained and 20 percent clear. However, only about 5 percent is clear mica by Indian standards of grading. The United States and the United Kingdom of Great Britain and Northern Ireland received all exports of mica from Argentina in 1942. In 1940 and 1941, Japan, Germany, and Italy imported large amounts of Argentina mica. Japan took all classes and grades, but Germany and Italy imported only the stained and better grades. A large proportion of the Italian quota in 1941 was sent to that country by airplane; it has been reported that the ship carrying most of the German imports for 1941 was intercepted by the British.

Australia.—Production has been limited almost entirely to muscovite from deposits in Northern Territory. Small quantities for grinding have been produced in Queensland, New South Wales, South Australia, and Western Australia. Most of the splittings come from India, although there is a small domestic splittings industry. In 1941 the Minister of Trade and Customs acquired all mica produced in Northern Territory, and in 1942 control and distribution of mica passed to the Comptroller of Mineral Products. Prices are fixed by the Commonwealth Price Commission. Consumption of clear and slightly stained mica increased in 1942, and it was necessary to import mica to satisfy domestic demands.

Brazil.--Mica comes chiefly from eastern Minas Gerais, although a small quantity of good-quality material also is mined in Baia and São Paulo. Mining methods are primitive, and considerable effort has been made to increase production by applying more efficient methods of mining and transportation. In 1942 Brazil exported 866 metric tons of mica, of which the United States received 776 tons and

the United Kingdom the remainder.

Canada.—Canada, which has been one of the two important world sources of phlogopite mica, entered the field of muscovite producers in 1942. Extensive deposits of white mica have been

found near Eau Claire, Nipissing County, Ontario.

Arrangements have been completed between the United States and Canada for the Colonial Mica Corporation of New York to act as sole buyer of the strategic grades of mica from these properties. production of phlogopite mica was essentially the same as in 1941.

Ceylon.—Here the right to mine mica is sold by authorized Government agents, and the areas must be approved by the Government mineralogist. Charges for mining are to be 5 percent of the value of the mica removed. The entire output for 1942 was bought by the British Ministry of Supply for use by the United Nations Joint Mica Commission.

India.—India is the most important producer of strategic mica (muscovite sheet and splittings), supplying about 75 percent of total world production of this grade. The producing areas are concentrated chiefly in the eastern part of the country, although a few small phlogopite deposits in the Travancore district of southwestern India

are being developed.

Indian block mica has been shipped chiefly to the United Kingdom and the United States, the two countries at times having taken threefourths of the total of such exports even before the war. Japan bought heavily from India up to 1940, when an unofficial but effective embargo was placed against such shipments. It is believed that a large portion of Japanese purchases was for reshipment to Italy and Germany. During the first quarter of 1941 only enough lowgrade mica was shipped to Japan to prevent official protests, and in July 1941 the embargo, still not announced, again went into effect. At the same time restrictions on shipments of mica to the United States were relaxed to the extent of omitting inspection of shipments at the mine, which simplified procedure and provided for quicker and more efficient handling.

Exports of mica from India in 1942 (which are the only available measure of production), as reported by the Bureau of Foreign and Domestic Commerce, were 14,398 metric tons, of which 13,155 tons were block and splittings and the remaining 1,243 tons consisted of ground, scrap, or waste. The United States received 5,451 metric tons of the Indian production, the United Kingdom of Great Britain and Northern Ireland 8,809 tons, and Australia and the other Allied

Nations the remaining 138 tons.

Madagascar.—Madagascar continued as the largest source of strategic phlogopite mica, but the United States received imports only in March and April. The principal deposits are in the extreme south end of the island. However, because of adequate stocks and restricted use, there was mica enough of this type to satisfy present

requirements and to maintain an adequate stock pile.

Mexico.—Mica has been produced in Mexico for only a relatively short time, although the existence of deposits has been known for a Most of the deposits are of the phlogopite variety, although some biotite and muscovite also have been found. tion for the latter half of 1942, the only period for which statistics are available, was 44 metric tons of phlogopite, all of which was exported to the United States.

New Zealand.—Muscovite-mica deposits of considerable size were discovered in south Westland (west coast of the South Island) at an altitude of 4,000 to 5,000 feet. Samples were of excellent quality, and access roads are being constructed, as there is an assured though

small domestic market for the finished product.

Peru.—Mica is the youngest mining enterprise in Peru, where deposits have been found along the Pacific coast and have been developed in an area 14 miles long by 7 miles wide. It has been estimated that with present mining equipment, plus access roads and

trucks, 20 tons of trimmed mica can be produced monthly.

Portugal.—Production in Portugal is mainly scrap mica from numerous small deposits and a small amount of good-quality amber sheet mica in small sizes. The estimated annual production is 350

short tons of scrap and 40 tons of amber sheet.

U. S. S. R.—Information on production of mica in the U. S. S. R. is very meager. Production statistics have not been available since 1935. Deposits are widely distributed and have been found in Archangel (Karelia), on the Kola Peninsula, in the Volyn provinces on the Black Sea coast, in the Urals, and in Siberia. The Siberian deposits in the Mama River district, the northern Baikal region, and Transbaikalia are said to furnish the major portion of the muscovite production. It is estimated that the Soviet Republic produces enough mica to meet its requirements.

# SALT

# By F. E. HARRIS AND K. G. WARNER

#### SUMMARY OUTLINE

	Page		Page
Summary		Stocks, seasonal demands, and capacity for	1480
Salient statistics Production	 1477 1478	production of commercial salt Resources	1481
States		Distribution and consumption Uses	. 1482 . 1483
Methods of manufactur Rock salt	 1479	Changes in the industry	1486
Evaporated salt	 1479	Imports and exports	. 1486 1488
Pressed blocks	 1480	World Production	

#### SUMMARY

Salt has contributed substantially to the war program; and, as might be expected with intensification of the war, a high record of production was attained in 1942, although the increase over 1941 was not nearly so great as that of 1941 over 1940. Gains occurred in all three types of salt output, the greatest being in salt of brine—9 percent; output of rock salt gained 7 percent and evaporated salt 6 percent. The increase in total salt was 8 percent. Demands of the chemical industry and for the manufacture of magnesium metal caused the largest increases in output of salt in 1942.

Salient statistics of the salt industry in the United States, 1935-39 (average) and 1940-42

	1935-39 (average)	1940	1941	1942
Sold or used by producers:  Manufactured (evaporated)short tons In brinedo Rock saltdo	2, 507, 374	2, 782, 741	3, 330, 106	3, 517, 832
	4, 205, 587	5, 311, 671	6, 771, 436	7, 373, 165
	1, 947, 254	2, 265, 548	2, 619, 087	2, 802, 287
Total: Short tons Value <sup>1</sup> A verage per ton <sup>1</sup>	8, 660, 215	10, 359, 960	12, 720, 629	13, 693, 284
	\$23, 405, 612	\$26, 474, 619	\$33, 620, 376	\$38, 144, 234
	\$2. 70	\$2. 56	\$2. 64	\$2. 79
Imports for consumption:  For curing fish short tons.  Value short tons.  Value short tons.  Value short tons.  Value short tons.	<sup>2</sup> 21, 250	2 12, 965	7, 426	<sup>2</sup> 6, 434
	<sup>2</sup> \$43, 722	2 \$25, 174	\$30, 058	<sup>2</sup> \$17, 667
	1, 385	1, 024	1, 110	367
	\$11, 813	\$6, 601	\$12, 156	\$4, 138
	24, 131	16, 413	6, 896	953
	\$55, 876	\$59, 029	\$17, 021	\$7, 496
Total:	46, 766	30, 402	15, 432	7, 754
	\$111, 411	\$90, 804	\$59, 235	\$29, 301
	90, 214	147, 044	123, 195	118, 424
	\$521, 652	\$699, 340	\$807, 925	\$892, 160
Apparent consumption 3short tons_	8, 616, 767	10, 243, 318	12, 612, 866	13, 582, 614

Values are f. o. b. mine or refinery and do not include cost of cooperage or containers.
 Includes salt in bags, sacks, barrels, or other packages—1938: 93 tons valued at \$673; 1940: 6 tons, \$12; 1942; 122 tons, \$1,200.
 Quantity sold or used by producers plus imports minus exports.

Of the dry salt produced in the decade 1932-42, evaporated salt has averaged 56 percent and rock salt 44 percent of the annual totals, the proportions having been maintained rather consistently through-

out the period.

Increased demand was experienced not only by the largest producers but also by many of the smaller operators, who reported active demand throughout the year. Wage increases ranged from 10 to 50 percent. No strikes were reported, but labor was scarce, particularly in the less-populated areas. Cost of material was reported to be high; in one locality the price of bags increased 300 percent. Many operators, particularly the smaller, stated that rising wages and costs of materials handicapped their business, inasmuch as the selling price was unchanged. Several plants closed, temporarily at least, the time of reopening to depend on the ability to obtain labor and on the selling price.

PRODUCTION

Salt was produced in 86 plants of 64 companies in 1942, operating in 14 States and Puerto Rico, compared with 83 plants of 65 companies in 1941. Of these plants, 66 produced evaporated salt and 20 rock salt; 11 of the plants in 7 States produced all the brine.

The International Salt Co. leads in rock-salt production as well as in total dry salt output. Morton Salt Co. leads in output of evaporated salt and is second in total dry salt production. Leslie Salt Co. is the largest producer of solar salt. Morton Salt Co. has some rocksalt interests, and International Salt Co. also produces some evaporated salt.

States.—Michigan again led in total production of salt as well as in output of the evaporated type, and New York led in rock-salt production; together, these States supplied 49 percent of the Nation's output of commercial salt. Grouped as a section, the Middle West (Kansas, Michigan, and Ohio) supplied 55 percent.

Salt sold or used by producers in the United States, 1940-42, by States

		1940	- 1 -		1941			1942		
State	Quantity			Quan	tity		Quan			
	Short tons	Percent of total	Value	Short tons	Percent of total	Value	Short tons	Percent of total		
California. Kansas. Louisiana Michigan. New Mexico. New York. Ohio. Oklahoma Puerto Rico. Texas. Utah West Virginia Other States 3	469, 354 684, 053 1, 132, 594 2, 863, 035 13, 915 2, 117, 671 2, 080, 133 (2) 11, 724 402, 165 71, 472 144, 312 369, 532	(1) 20 20 (2) (1) 4 1 1 4 4	7, 479, 905 41, 573 6, 523, 775 2, 781, 599 62, 645 792, 214 191, 263 701, 953 183, 799	781, 014 1, 242, 242 3, 620, 649 16, 641 2, 719, 586 2, 510, 096 10, 743 14, 444 656, 569 107, 079 143, 780 413, 154	(1) (2) (2) (2) (2) (2) (1) (3) 5 1 1 3	10, 975, 872 51, 514 7, 416, 734 3, 367, 544 42, 737 72, 220 1, 713, 508 196, 413 792, 104 195, 145	860, 083 1, 332, 129 3, 946, 591 13, 956 2, 722, 670 2, 711, 188 8, 305 18, 198 821, 111 110, 871 140, 216 461, 646	(1) (20) (20) (1) (1) (1) (1) 6 1 1	3, 381, 85 12, 583, 96 47, 26 8, 158, 14	
	10, 359, 960	100	26, 474, 619	12, 720, 629	100	33, 620, 376	13, 693, 284	100	38, 14	

Less than 0.5 percent.
 Included under "Other States."
 1940: Colorado, Oklahoma, and Virginia; 1941: Colorado and Virginia; 1942: Colorado, Nevada, and

Methods of manufacture.—As in the past, the salt was obtained from natural brine of wells and ponds, by forcing water into salt beds and withdrawing it as brine, from sea water, and from bedded deposits that are mined. Salt is evaporated by several methods, as given in the accompanying table.

Salt sold or used by producers in the United States, 1941-42, by methods of manufacture

	19	41	1942		
Method of manufacture	Short tons	Value	Short tons	Value	
Evaporated: Bulk:					
Open pans or grainers	501, 236	\$4, 100, 293	500, 758	\$4,607,104	
Vacuum pans	2, 192, 142	12, 596, 983	2, 234, 633	13, 916, 501	
Solar	454, 397	1, 577, 740	542, 087	2, 238, 604	
Pressed blocks	182, 331	1, 505, 040	240, 354	2, 228, 062	
Rock:			1		
Bulk	2, 562, 386	8, 300, 562	2, 734, 797	9, 054, 447	
Pressed blocks	56, 701	461, 265	67, 490	569, 014	
Salt in brine (sold or used as such)	6, 771, 436	5, 078, 493	7, 373, 165	5, 530, 502	
	12, 720, 629	33, 620, 376	13, 693, 284	38, 144, 234	

Rock salt.—The output of rock salt came from 20 plants in 8 States, chiefly New York, Louisiana, Kansas, Michigan, and Texas, in order of output; California, New Mexico, and Utah also produced.

Rock salt sold by producers in the United States, 1938-42

Year	Short tons	Value	Year	Short tons	Value
1938 1939 1940	1, 901, 861 2, 035, 157 2, 265, 548	\$6, 252, 081 6, 496, 807 7, 384, 839	1941 1942	2, 619, 087 2, 802, 287	\$8, 761, 827 9, 623, 461

Evaporated salt.—Sixty-six plants in 13 States and Puerto Rico supplied evaporated salt, as given in the accompanying table, compared with 61 plants in 12 States and Puerto Rico in 1941.

Evaporated salt sold or used by producers in the United States, 1941-42, by States

	19	41	1942		
State	Short tons	Value	Short tons	Value	
California Kansas Louisiana Michigan <sup>1</sup> New York Ohio Oklahoma Puerto Rico Texas Utah West Virginia <sup>1</sup> Other States <sup>2</sup>	38, 138 1, 129, 714 438, 451 481, 364 10, 743 14, 444 232, 643 99, 426	\$2, 171, 889 2, 119, 917 294, 558 6, 027, 100 4, 006, 454 2, 817, 183 42, 737 72, 220 1, 190, 684 172, 954 172, 954 172, 256 19, 780, 056	463, 357 335, 188 62, 825 1, 154, 732 425, 216 464, 841 8, 305 18, 198 304, 403 103, 334 140, 216 37, 217 3, 517, 832	\$2, 286, 815 2, 628, 892 460, 919 6, 846, 855, 825 3, 413, 416 35, 132 103, 071 1, 584, 008 256, 124 822, 794 196, 413	

<sup>1</sup> Includes a quantity of salt contained in brine for chemical use reported as evaporated salt. evaporated salt. 2 1941: Colorado and New Mexico; 1942: Colorado, Nevada, and New Mexico.

Pressed blocks.—Hydraulically compressed blocks from both evaporated and rock salt totaled 307,844 short tons valued at \$2,797,076 in 1942. They were produced by 8 rock-salt and 20 evaporated-salt

plants.

Some of the blocks for domestic consumption contain small amounts of chemicals for their medicinal value. Blocks of iodized salt are produced for conditioning cattle, although the demand for salt of this type is not nearly so great as for those to which sulfur and other chemicals have been added. Some of the blocks contain potassium. At one of the potash mines where salt is a byproduct sold to another company for distribution, some of the salt, which contains about 20 percent potash, is made into blocks simply by pouring a strong brine over a boxful of the salt, which has been ground to ¼-inch mesh and under. When dry the blocks are too hard to be broken by hand, although they will disintegrate when out of the boxes and exposed to weathering and must be sold in the containers.

Pressed-salt blocks sold by original producers of the salt in the United States, 1938-42

	From evaporated sa		From ro	ck salt	Total		
i ear	Short tons	Value	Short tons	Value	Short tons	Value	
1938	136, 699 152, 121 152, 267 182, 331 240, 354	\$1, 116, 272 1, 136, 527 1, 193, 237 1, 505, 040 2, 228, 062	36, 258 39, 242 40, 171 56, 701 67, 490	\$281, 109 263, 300 282, 435 461, 265 569, 014	172, 957 191, 363 192, 438 239, 032 307, 844	\$1, 397, 381 1, 399, 827 1, 475, 672 1, 966, 305 2, 797, 076	

Salt content of brine.—Salt in brine produced at 11 plants in various parts of the country increased from 6,771,436 short tons in 1941 to 7,373,165 tons in 1942. Most of the brine was used as the source of basic chemicals. The Federal Reserve Board index for chemicals rose from 137 in 1941 to 173 in 1942.

# STOCKS, SEASONAL DEMANDS, AND CAPACITY FOR PRODUCTION OF COMMERCIAL SALT

In general practice, salt producers do not attempt to keep large stocks on hand. However, the practice varies somewhat according

to the types of salt sold.

Most evaporated salt is shipped as rapidly as it is refined and packed. The plants have bins only to accommodate near-future requirements to guard against temporary delays from interruptions in their plants. At those evaporated-salt plants where storage is provided, it is reported that the bins have a capacity of only 1,000 to 6,000 tons, which may represent requirements for only 4 or 5 days, or at the most a month's supply.

A notable exception is the storehouses on the shore of Lake Michigan, where several plants stock their salt in the winter awaiting water transportation. Here the supply may total 10,000 to 40,000 tons of

evaporated salt stored during the off-peak shipping season.

Solar salt presents a somewhat different problem. Here the salt necessarily must be stored in great piles in the open. For climatic reasons, solar salt is harvested from ponds chiefly in the last 3 months

SALT 1481

of the year. The salt, stacked in huge piles, the steep sides of which become crusted and impervious to rain, represent 9 to 11 months'

supply.

Rock-salt producers find that the best and cheapest way to store salt is in the ground, and surface stocks are virtually nonexistent. Therefore, at most mines the salt either is shipped out as rapidly as it is mined, crushed, and screened, or "finished," or it is blasted down in a room in the mine and left there until needed above ground. Such underground piles may be enough for 6 to 8 months' supply. One of the mines that normally in the past had about 35,000 tons of various grades shipped the salt in 1942 as mined. Surface bins are merely for loading, and the salt may be in them only 4 or 5 days or less. One operator that "stores" in the mine has loading bins of about 1,000 tons, which is less than a day's production. Exceptionally small bins of 100 to 250 tons capacity are maintained to store various sizes of the screened rock salt to satisfy demands for sizes not being made currently.

In the matter of seasonal demands, most salt producers say that in the second half of the year the demand for both evaporated and rock salt is heavier than in the first half. Some have slightly higher demands in the spring and fall but not enough to affect their sup-

plies appreciably.

A Bureau of Mines study reveals that plant capacity for rock-salt production totals about 5,200,000 tons and for evaporated salt about 4,400,000 tons. Therefore, it is evident that in 1942 the rock-salt facilities operated at 54 percent and evaporated salt at 80 percent of capacity. (These capacities are predicated on well-ordered production systems and do not make allowance for idleness during break-downs, delays in obtaining critical materials for repairs, or other causes.)

Theoretically it is easier to expand the capacity for rock salt than that for evaporated salt, as it becomes chiefly a matter of how speedily

the loose material can be hoisted to the surface.

In some solar salt playas and marshes there is an unlimited supply of crude salt that requires only loading. Most of these, however, are not near marketing centers or shipping points, and the transportation makes a commodity costly that is very cheap at the source.

#### RESOURCES

Fortunately for the United States, when it is involved in a war that depends so much on chemicals in one form or another, the country has an inexhaustible supply of salt and a well-established

chemical industry.

The Middle West has huge underground stores of salt within three of its States. Kansas has many millions of tons in reserve. Michigan has deposits in three separate sections; wells annually supply thousands of tons of strong salt brine, and in addition there are rock-salt mines. Ohio has no rock-salt mines, but it apparently has a plentiful salt supply although the brine raised is not as strong as that of Michigan.

The Pacific coast depends largely on the ocean, and therefore its supplies of solar salt are unlimited. Additional resources in Cali-

fornia are the desert playas and rock-salt deposits,

In the South the huge domes of almost pure salt in Louisiana and Texas can supply requirements for a long time. The domes usually range from 1.2 to more than 2 miles in diameter and are thousands

of feet in thickness.

The East, although not destitute of salt, is the least fortunate of all sections of the United States. New York, the leading source, has large deposits of rock salt that yield mined salt and brine for making chemicals and evaporated salt after recrystallization. However, these sources are about 200 miles inland. In the past the eastern seaboard has obtained salt from Canada and the West Indies; but, with difficulties in shipping because of the war, imports from these former sources have dwindled in the past few years. The western part of Virginia has supplies of natural brine, which is used solely for the manufacture of chemicals. West Virginia has resources of brine from which it produces evaporated salt.

Some States have large deposits of good salt, but economic conditions do not favor their development. For instance, New Mexico has numerous salt deposits but only a few small, scattered plants to supply local demands. Enormous reserves are present, but no large-scale consuming industries are near enough to encourage

development.

# DISTRIBUTION AND CONSUMPTION

Although the figures in the accompanying table cover original shipments from the producers and do not show reshipments, they indicate approximate salt consumption in the various States.

Distribution (shipments) of evaporated and rock salt in the United States, 1941-42, by States of destination, in short tons

Destination	194	11	1942		
	Evaporated	Rock	Evaporated	Rock	
Alabama	7, 613	32, 790	0 420	FO. 005	
Alizula	10.050		8, 432	58, 835	
Arkansas	0.000	3, 031	11,814	2, 673	
Camornia	978 417	26, 968	8,011	28, 144	
Colorado	00,000	29, 594	277, 696	54, 578	
Connecticut	29,086	12,774	39, 535	23, 349	
Delaware		6, 796	16,020	7, 239	
District of Columbia	4, 599	23, 655	3, 921	11, 361	
Florida	5, 517	1, 511	5, 361	2,060	
Georgia.	6, 243	24, 389	7, 618	25, 601	
Idaho	19, 145	50, 647	17, 766	55, 541	
Illinois	11, 181	1, 398	13, 949	1, 653	
Indiana		163, 994	257, 710	184, 395	
Indiana Iowa	80, 798	58,066	90, 534	61, 002	
IowaKansas	98, 653	88, 771	116,022	99, 564	
Vontuebre	39, 225	211, 447	51, 543	175, 486	
Kentucky	38, 195	17,654	38,036	29, 673	
Louisiana	4,833	71,012	5, 670	76, 972	
Maine	10, 212	31, 476	11, 484	40, 123	
Maryland	29, 977	26, 277	29, 399	28, 795	
Massachusetts		43, 266	58, 101	52, 712	
Michigan.	356, 194	60, 201	384, 960	54, 219	
2011HITESOLA	114,029	66, 290	120, 752	66, 255	
WISSISSIPPI	2, 624	31, 493	3, 559	32, 447	
M1880411	76, 748	51, 991	79, 429	65, 553	
Montana	17, 537	6, 494	20, 608	6, 692	
Nebraska	30, 112	46, 171	45, 832	51, 129	
Nevada	3, 948	316	43, 569	29,000	
New Hampshire	8, 544	34, 330	9, 260	41, 273	
New Jersey	83, 200	161,044	84, 366	153, 887	
New Mexico	7, 974	17, 548	9, 746	14, 146	
New York	228, 127	449, 549	204, 361	429, 375	
North Carolina	49, 257	55, 740	53, 326	53, 561	

Distribution (shipments) of evaporated and rock salt in the United States, 1941-42, by States of destination, in short tons—Continued

Destination	194	1	1942		
	Evaporated	Rock	Evaporated	Rock	
North Dakota Ohio Oklahoma Oregon Pennsylvania Rhode Island South Carolina South Dakota Tennessee Texas Utah Vermont Virginia Washington West Virginia Wisconsin Wyoming Other 1	13, 225 201, 234 35, 080 29, 354 156, 657 11, 760 8, 584 16, 209 22, 558 244, 055 14, 902 57, 585 116, 187 171, 727 132, 958 86, 953 3, 330, 106	4, 116 82, 333 33, 671 112, 306 10, 789 17, 673 11, 483 47, 547 166, 452 3, 218 7, 648 7, 648 50, 120 558 60, 980 25, 743 1, 768 76, 881	11, 594 216, 898 33, 312 29, 684 150, 806 10, 071 8, 513 19, 683 26, 681 315, 777 22, 135 4, 982 52, 544 125, 528 167, 864 129, 307 7, 755 56, 353	5, 110 95, 172 36, 422 101, 980 10, 472 22, 519 12, 480 49, 986 8, 675 63, 790 941 75, 171 26, 553 2, 073 81, 355	

<sup>&</sup>lt;sup>1</sup> Includes production of Puerto Rico (evaporated salt); exports to Africa, Asia, Canada, Central America, Mexico, Newfoundland, South America, West Indies, and other countries; shipments to Alaska, Hawaii, Puerto Rico, and Virgin Islands; and some shipments to unspecified destinations.

Salt shipped to noncontiguous Territories of the United States, 1941-42

	19	41	1942		
Territory	Short tons	Value	Short tons	Value	
Alaska Hawaii Puerto Rico Virgin Islands	5, 929 2, 909 1, 629 32	\$103, 455 78, 996 50, 046 1, 775	4, 829 2, 668 1, 004 53	\$94, 646 109, 222 34, 100 3, 562	

Consumption trends have changed in the last few years, owing in part to the shift of consumers from one center to another and in part to the establishment of entirely new centers of consumption. The average annual shipments for 1931–36 show that New York received the largest total of dry salt of the two types; Illinois was next in receipts, followed by California, Michigan, Texas, and Kansas. In the evaporated-salt market, Illinois received the largest average annual total in 1931–36, followed by California, Michigan, New York, Texas, and Kansas. In rock-salt receipts, New York led, followed by Illinois, Kansas, Texas, Michigan, and California.

#### USES

Our first full year of war witnessed an increased use of salt for all the war purposes discussed in the chapter on Salt in Minerals Yearbook, 1941; and in addition there were a few new and modified uses, both military and civilian.

Less salt was used for industrial meat packing in 1942 than in 1941, chiefly because of greater demand for canned instead of salt-treated meat for camps at home and overseas. Also, more meat was packed and canned on the farms in 1942. Although canning requires less salt than packing, about 10,000 tons more salt were used in industrial

canning. Home canning of various products made greater demands also, as evidenced by the large increase in table salt and other household uses.

Chemicals were made not only from brine but from thousands of tons of "dry" salt as well. Chemicals from salt have long been used in many medicines, and recent uses include the groups of sulfa and

vitamin drugs.

Both elements of salt are used in many of our war materials, as exemplified by the following: Both sodium and chlorine are needed in making tetra-ethyl lead for high-octane gasoline, production of which increased enormously in 1942. Sodium and chlorine are being used increasingly for synthetic-rubber manufacture. Many dyestuffs require both. Cotton linters for smokeless powder are treated with chlorine for bleaching and sodium for purifying. The cleaning and degreasing of metal tools, parts, and shells require both elements.

Fighting in the hot jungles has created a new application for salt and derivatives thereof. Chlorine is an effective spray for eliminating mosquitoes and other jungle insects. The men fighting in the tropics are supplied with salt tablets to combat heat cramps caused by loss of salt through perspiration. Also, Navy regulations provide for salt to be supplied to the men on ships, needed by men not only when in tropical waters but when working below decks in the hot engine rooms.

As a result of wartime requirements, chlorine output in 1942 was greater than it has ever been; even with the curtailment of civilian supplies, it exceeded the 1941 output by more than 30 percent. Because of lack of steel containers in which chlorine is "packaged" and tank cars to transport it, the chemical cannot be stocked ahead of the demand, and the suppliers must keep a watchful eye on requirements and prompt return of the containers.

Salt sold or used by producers in the United States, 1941-42, by classes and uses, in short tons

		1941			1942	
Use	Evapo- rated	Rock	Brine	Evapo- rated	Rock	Brine
Chlorine, bleaches, chlorates, etc	1,500 1 91,052	619, 489 37, 798 17, 086	496, 128 6, 226, 821	843, 970 218 78, 752 28, 118	704, 227 20 44, 485 13, 360	654, 686 6, 670, 62
Other chemicals Pextile processing Hides and leather Meat packing	61, 924 63, 523 3 79, 063 3 422, 017	218, 570 75, 744 3 139, 041	(2)	60, 849 41, 535 118, 976	254, 198 77, 189 182, 650	(2)
Butter, cheese, and other dairy products Canning and preserving	34, 939 105, 179 128, 143	6, 363 4, 664 16, 356		28, 908 94, 050	322, 938 32, 007 6, 642 19, 223	
Other food processing Refrigeration Livestock Lighways, railroads, dust and ice control	172, 068 30, 489 519, 027 26, 382	14, 827 94, 790 254, 031 167, 126		32, 536 556, 885	17, 857 153, 010 246, 340 197, 751	
Pable and other household	420, 532 165, 610 50, 523	75, 289 187, 445 21, 261		460, 020 171, 433 81, 700	224, 764 203, 757 16, 968	
Other uses	187, 236	41, 288 218, 678 2, 619, 087	48, 487 6, 771, 436	31, 990 117, 430 3, 517, 832	33, 347 51, 554 2, 802, 287	47, 858 7, 373, 165

Some salt used for dyes and organic chemicals included under "Chlorine."
 Included under "Other uses."
 Some salt used for hides and leather included under "Meat packing."

SALT 1485

For many years most of the chlorine produced in the United States has originated in New York State. Little more than a decade ago New York still produced about half of the national output, and Michigan and Ohio were large producers also. The trend has changed, and in recent years the Midwest has become the largest chlorine-producing center, and new plants are to be found in the South and West. To the many uses for chlorine mentioned in the Salt chapter for 1941 may be added smoke screens and smoke bombs. Additional quantities of chlorine compounds were used in plastics, special waterand mildew-proofing waxes, fire extinguishers, and disinfectants.

With a view to utilizing some of the vast salt deposits in Kansas for chlorine and the petroleum from nearby oil fields for cheap power for steam generators, investigators (George W. Stratton and Delos E. Winkler) at the University of Kansas developed a method of making carbon black from natural gas and chlorine. From 1,000 cubic feet of the mixture, it is said, 30 pounds of carbon black are produced.

The process is not yet commercial.

Sodium compounds derived from salt have many important uses in the form of soda ash and caustic soda; the largest use for soda ash is in glassmaking, and for caustic soda in rayon-fabric manufacture. Sodium compounds will also assist in the removal of unwanted sulfur compounds from petroleum products and are essential raw materials for phenolic resins. They assist not only in making rayon cord for rubber tires but are used also to dissolve the cord fabric in the tires, when the rubber is to be reclaimed.

Increases in output of magnesium metal made by methods that require large tonnages of salt led to corresponding increases in salt

production in 1942.

The use of common salt for glazing ceramics has increased in the last year or two, because of the increased use of such ware for cooking utensils, structural building units, and other purposes, and because

salt is said to be the simplest and cheapest of all glazes.

Statistics show that the use of salt on roads is continuing. It is applied mainly to secondary roads where the salt is bladed into the clay or gravel of the top layer. Emphasis has been placed upon the advantage of such roads in cold weather or during seasonal changes in temperature. In Cuba in 1942 salt was used on runways of air fields. It was added to the layer of clay and gravel under the top dressing of asphalt to make it more elastic and thus obviate cracking. Usually in the United States salt-treated roads have no top dressing, although a successful long-used road in Virginia was made by finishing with a thin layer of asphalt over the salt-treated layer.

Further interest in salt as a fertilizer for beets and mangolds was created by articles in the press 2 which advised all growers of beets on muck soil to make every acre produce its best in 1942 by applying 1,000 pounds of salt an acre in addition to the regular fertilizer used. It is claimed that 500 to 1,000 pounds of salt so applied may increase the yield from 13 tons to 21 tons an acre. Salt has also been utilized instead of potash on mangolds, sugar beets, and cabbage at the rate of 500 pounds an acre. Moreover, when employed in conjunction with a good dressing of sulfate of ammonia, salt is said to act as well

<sup>&</sup>lt;sup>1</sup> Chemical and Engineering News (Am. Chem. Soc.), vol. 20, No. 20, October 25, 1942, p. 1317.

<sup>2</sup> Sugar Beet Journal, March 1942, p. 116; Chemical and Engineering News (Am. Chem. Soc.), vol. 20, No. 20, October 25, 1942, p. 1308,

as muriate of potash. Sandy soils (often deficient in potash) are said to be improved by its application; salt has also proved most effective on light and medium soils.

## CHANGES IN THE INDUSTRY

The plant of Oklahoma Salt Industries, Inc., which began producing in 1941 at Sayre, Okla., suffered heavy loss by fire and was out of operation after September 26, 1942; it is being rebuilt. The Stauffer Chemical Co., which sold its solar salt works at Redwood, Calif., to the Leslie Salt Co. the latter part of 1940 but continued to operate in 1941, did not produce in 1942. The Leslie Salt Co., San Francisco, has enlarged its solar-salt fields on the Pacific coast and in 1942 also produced from a deposit of rock salt at Fallon, Nev. The Mullet Island Salt Co., Niland, Calif., began producing in 1942; and the Defense Plant Corporation, at Death Valley Junction, Calif., produced solar salt for 3 months of 1942. The Puerto Rico Salt Works, Inc., Mayaguez, P. R., reported in detail its three plants in Guaypao, Boqueron, and Llanos Costa Counties, instead of including them in a consolidated report as formerly. Works of Marcelino Ramos, Ensenada, P. R., made no sales in 1942. In March 1943, the Morton Salt Co., Chicago, bought the Worcester Salt Co., which operated an evaporated-salt plant at Silver Springs, N. Y.

## IMPORTS AND EXPORTS 3

From 1938 to 1942 imports averaged about 0.25 percent and exports a little more than 1 percent of production. Most of the imports are received on the Atlantic coast, where no salt plants operate.

In normal times pressed blocks have not been exported, but since lend-lease has been in effect some shipments of blocks have been made overseas. This is not apparent, however, in the accompanying table, as the exports are not shown by classes.

Salt imported for consumption in the United States, 1938-42, by classes

	In bags, sac	eks, barrels,	Bulk					
• Year	or other packages (dutiable)		Duti	able	Free (used in curing fish)			
	Short tons	Value	Short tons	Value	Short tons	Value		
1938	654 2, 121 1, 024 1, 110 2367	\$8, 228 14, 977 6, 601 12, 156 24, 138	17, 849 28, 451 16, 413 6, 896 953	\$45, 897 58, 540 59, 029 17, 021 7, 496	1 21, 010 15, 461 112, 965 7, 426 16, 434	1 \$47, 800 27, 700 1 25, 174 30, 058 1 17, 667		

Includes salt in bags, sacks, barrels, or other packages as follows—1938: 93 tons valued at \$673; 1940: tons, \$12; 1942: 122 tons, \$1,200; 1939 and 1941: None reported.
 Includes 98 pounds valued at \$3 imported into Alaska free for the U. S. Government.

<sup>&</sup>lt;sup>3</sup> Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

# Salt imported for consumption in the United States, 1941-42, by countries

	194	11	1942		
Country	Short tons	Value	Short tons	Value	
North America: Canada	695	\$6, 334	1,358 28	\$12,430 144	
West Indies: British: Jamaica	1, 248 7, 276	7, 276 29, 287	4, 142	14,767,	
Other British Netherlands: Curação Europe: France	85 6,027	194 14, 018	56	260	
United Kingdom <sup>1</sup> Africa: Egypt	101	2, 126	2,170	1,700	
	15, 432	59, 235	7,754	29, 301	

<sup>&</sup>lt;sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

# Salt exported from the United States, 1941-42, by countries

	194	L	1942		
Country	Short tons	Value	Short tons	Value	
North America: Bermuda	21	\$582	141	\$6, 295	
Canada	68, 288	287, 411	72, 617	321, 907	
	00, 200	201, 111	.2, 51.	021, 001	
Central America: British Honduras	5,548	5, 435	673	7,715	
Guatemala	19	382	25	629	
Honduras	128	3,642	119	2, 393	
Nicaragua	362	5,654	190	3, 617	
Donomo:	302	5,552		·	
Republic of	148	3, 111	27	1,917	
Canal Zone	887	27, 225	933	23, 794	
Greenland	5	107	2, 513	35, 835	
Iceland	8	483	34	2,008	
Mexico	4,742	67,700	5,686	88, 154	
Newfoundland and Labrador	408	6, 719	21, 899	106, 216	
West Indies:		7			
British	114	1,695	168	3, 302	
Cuba	12,950	143, 491	9,437	121, 725	
Dominican Republic	322	6, 843	111	2, 229	
Haiti	12	476	15	945	
Netherlands: Curação	116	5, 349	132	7,092	
Other North America	18	437	. 174	2,820	
South America:	10				
Argentina	472	4, 485	332	3, 409	
Brazil	157	3, 124	26	668	
Colombia	14	364	(1)	118	
Other South America	455	7, 796	819	27, 547	
Europe:	200	.,	5.00	,	
U. S. S. R	100	<u>.</u>	1,402	95,951	
Other Europe	1	51	-,		
Asia:	- 1				
China	7	969			
Hong Kong	61	1, 442			
Japan	26, 301	179, 543			
Philippine Islands	353	11, 169			
Other Asia	68	1,840	7	736	
Africa:	. ~ [	-,	, ,		
Liberia	774	18, 623	548	12,790	
Other Africa	118	6, 285	92	3,701	
Oceania:		,		.,	
British:	1				
Australia	(1)	34	I <b></b>		
New Zealand	158	2, 570	42	3, 182	
Other			4	425	
French	160	2,888	258	5, 040	
PICHCH					
	123, 195	807, 925	118, 424	892, 160	
	120, 200		,		

<sup>1</sup> Less than 1 ton.

#### WORLD PRODUCTION

Salt production in the United States represents roughly about onethird of the global production. It does not figure largely in international trade until converted into products. In the last decade the United States has doubled its output. The war has had its effect on a number of other countries. Salt production in Canada increased 17 percent in 1942 compared with 1941, part of the increase being attributed to greater demand for chemicals, especially chlorine. Free China produced 800,000 metric tons of salt during the first 9 months of 1942 and 1,152,000 tons in the year 1941. Statistics for occupied China have not been available for the last 2 years, but the salt fields have been worked actively. In 1941 Germany established a compulsory national salt cartel comprised of one rock-salt and two evaporated-salt associations. The Italian Empire has suffered important salt losses through the war, first, by the loss of its East African colonies, later by the loss of Libya, and more recently through damage done by bombings of the salt works near Trapani, Sicily. accordance with an agreement made in September 1942, Spain is to supply French Morocco with salt in exchange for phosphates from the latter country. Additional details regarding the salt industry in these and other countries have been recorded in various issues of Bureau of Mines Mineral Trade Notes—Confidential Series, between July 1942 and May 1943.

World production of salt, 1937-42, by countries, in metric tons <sup>1</sup>
[Compiled by B. B. Waldbauer]

7					<del>,</del>	
Country 1	1937	1938	1939	1940	1941	1942
North America:	1	1.00				
Canada	415, 994	398, 013	385, 550	420, 974	508, 787	597, 340
Costa Rica	4, 287	4,740	6,822	(2)	6,000	(2)
Dominican Republic	(2)	9, 286	9, 536	7, 500	14,700	(2)
Guatemala	12,610	10, 465	(2)	(2)	(2)	(2)
Mexico	82, 876	107, 701	(2)	(2)	(2)	(2) (2) (2) (2)
Panama		3, 332	4, 536	5, 199	2)	25
United States:	0,000	0,002	2,000	0, 100		
Rock salt	1, 841, 967	1, 725, 330	1,846,254	2, 055, 260	2, 375, 983	2, 542, 179
AOCK Sait						
Other salt	6, 541, 795	5, 555, 486	6, 570, 481	7, 343, 089	9, 163, 917	9, 880, 094
west indies.			}			1
British:						
Bahamas	2,000	17, 900	11,600	27,000	25, 400	(2)
Turks and Caicos Islands					ŀ	1
(exports)	50, 833	35, 578	47, 389	67, 028	48, 179	(2) (2) (2)
Cuba Netherlands (exports)	36, 806	57, 970	113, 398	113, 398	41, 909	(2)
Netherlands (exports)	2, 337	2,013	247	37	3, 226	(2)
South America:	.,	,			,,	
Argentina (railway shipments)	290, 084	264, 150	303, 321	292, 307	372, 689	(2)
Brazil	770, 403	788, 218	502, 203	(2)	550,000	25
Brazil Chile	36, 697	27, 772	39, 593	44, 317	57, 185	(2) (2) (2)
Colombia:	30,001	21,112	00,000	11,011	01,100	(-)
Rock salt	4, 211	4 010	3, 950	4, 703	4, 530	(2)
NOUK Salt		4,010				(2) (2)
Other salt	184, 609	199, 022	218, 134	228, 750	192, 249	(2)
Ecuador:				<b>(m</b> )	1	(8)
Rock salt	138			(2)	::-::-	(2) (2) (2)
Other salt	13, 800	13, 800	16, 145	29, 900	20, 207	(3)
Peru	39, 010	38, 451	39, 669	41, 326	46, 707	(2)
Venezuela	26, 298	22,658	20, 473	52, 540	(2)	(2)
Europe:	·	· ' i	,	,		
Bulgaria:					i	l
Rock salt	9, 745	10, 242	13, 168	15,000	(2)	(2)
Other salt	43, 602	66, 258		65,000	(2)	(2)
Czechoslovakia	165, 898		(2) (2)	(2)	(2) (2) (2)	(2)
O DOULIOSIO V GRAIGA	100,000	1.1,000		()	(7)	( ()

See footnotes at end of table.

<sup>4</sup> Department of Commerce, Foreign Commerce Weekly: November 14, 1942, p. 11.

World production of salt, 1937-42, by countries, in metric tons-Continued

Country	1937	1938	1939	1940	1941	1942
turope—Continued.						
France: Rock salt and salt from springs Other salt	1, 847, 179 490, 906	1, 264, 230 346, 046	(2) (2)	(2) (2)	(2) (2)	(2) (2)
Germany: Rock salt Other salt	2, 757, 242 608, 046	2, 694, 984 585, 326	(2) (2)	(2) (2)	(2) (2)	(2) (2)
Austria:		786	(2)	(2)	(2)	(2)
Austria: Rock salt Other salt Greece	908 169, 883 102, 285	93, 576 102, 057	(2) (2) (2)	(2)	(2) (2)	(2) (2) (2)
Rock salt	603, 798 952, 655	613, 870 885, 205	(2) (2)	(2) (2) (2) (2)	(2) (2) (2) (2) (2) (2)	(2) (2) (2) (2) (2) (2) (2)
Netherlands: Rock salt	1 270	1, 523	1, 753	(2)	(2)	(2)
Netherlands: Rock salt	132, 430 602, 746 4, 633	164, 266	(2) (2)	(2)	(2)	(2)
Poland Portugal (exports)	4 633	642, 875 6, 096	9, 289	11, 955	(2)	(2)
		18.0				1
Rock salt Other salt	308, 882	350, 618	(2) (2)	(2) (2)	(2) (2)	(2) (2)
Other salt	2, 077	1, 140	(4)		(*)	(9)
Spain: Rock salt	29, 673	150, 878	157, 784	206, 650	(2)	(2)
Rock salt Other salt Switzerland	120, 175 81, 969	102, 671 84, 049	157, 784 (2)	206, 650 463, 795 77, 000	(2) (2) (2)	(2) (2) (2)
Switzerland United Kingdom:	81, 969	84, 049	90,000	77,000	(²)	(2)
Great Britain:						
Great Britam: Rock salt Other salt Ireland, Northern: Rock salt Other salt	18, 666	19,974	(2) (2)	(2) (2)	(2) (2)	(2) (2)
Other salt	3, 101, 511	2, 651, 939	(2)	(2)	(2)	(2)
Ireland, Northern:	4 954	0 262	(2)	(2)	(2)	(2)
Other salt	4, 254 8, 818	2, 362 5, 757	(2)	(2)	(2) (2) (2)	(2) (2)
Yugoslavia	46, 323	52, 634	54, 213	(2)	(2)	3 28, 00
SIG.		200 510		050 714	(2)	(3)
Aden	360, 866 54, 677	282, 510 39, 319	294, 077 (2)	258, 714 (2)	(2) (2) (2)	(2) (2) (2)
Burma_ Ceylon_ China (including Manchuria) Chosen 4	38, 815	1 36, 490	37, 556	29, 973	(2)	(2)
China (including Manchuria)	43,000,000	4 3,000, 000 138, 000	43,000,000 138,000	43,000,000 138,000	51,152,000	\$ 6 800, 00
Chosen 4	138,000	138,000	138,000	3,000	(2)	(2) (2)
Cyprus 4India:	3, 000	3,000	3,000	3,000		(-)
The state Is a			1			
Rock salt	190, 103	191, 395	196, 503	(2) (2)	(2)	(2)
Other salt	1, 516, 984 26, 095	1, 372, 979	1, 320, 344 97 070	38 564	(2) (2) (2) (2) (2)	(2) (2) (2) (2) (2)
Indochina	193 558	193, 050	213, 526	38, 564 166, 000	(2)	(2)
British: Rock salt Other salt Portuguese Indochina Iraq	193, 558 1, 810	29, 527 193, 050 7, 907	1, 326, 544 27, 979 213, 526 9, 107	8, 779	(2)	(2)
Japan:		1	ı		(2)	(2)
Japan proper 7 Taiwan	535, 775 210, 471 75, 780	(2) (2)	(2)	(2)	2	(2) (2) (2)
Netherlands Indies	75, 780	90, 909	8 141, 208	8 388, 837	(2)	(2)
			1			1
Rock salt	727	444	645	599	(2)	(2)
Other salt	11, 717 48, 905	8, 065 (2)	8, 736 (2)	9,944	2	[ [2]
Syria 4	10,000	10,000	10,000	10,000	(2)	(2)
Thailand (exports)	107, 731 262, 226	10,000 156,268 247,293	95, 170 (²)	112, 197 (²)	(2) (2) (2) (2) (2) (2) (2)	(2) (2) (2) (2) (2) (2)
Palestine: Rock salt. Other salt Philippine Islands Syria 4 Thailand (exports) Turkey	262, 226	247, 293	(2)	(2)	(2)	
Africa: Algeria Algeria Belgian Congo. Canary Islands 4 Egypt (exports) Ethiopia: Rock salt 4 French West Africa (exports) Kenya Colony Libya (Italian Africa): Cyrenaica 4 Tripolitania 4 Mauritius 4 Morocco, French Nigeria 4	63, 767	74, 630	(2)	(2)	(2)	(2)
Belgian Congo	1,004	1.013	(2) (2)	(2) 1, 038	(2) (2) (2) (2) (2) (2) (2) (2)	(2) (2) (2) (2) (2) (2) (2) (2)
Canary Islands 4	1, 004 2, 000 276, 735	2,000	2,000	2,000 9 168,591 10,000 (2) 9,425	(2)	(2)
Egypt (exports)	276, 735	284, 949 10, 000	442, 532 10, 000	100,091		(2)
French West Africa (exports)	643	51	(2)	(2)	(2)	(2)
Kenya Colony		3, 250	(2)	9, 425	(2)	
Libya (Italian Africa):	10.000	10 000	10,000	10,000	(2)	(2)
Crinolitania 4	10,000 20,000	10,000 20,000	20,000	20,000	(2) (2) (2) (2) (2) (2)	(2) (2) (3) 4 55, 00
Mauritius 4	1,500	1,500	1,500	1,500	(3)	(2)
Morocco, French	11, 207	909	(2)	(2) 400	(2)	4 55,00
Nigeria 4	400 2,605	400 6, 448	400 6,628	251	1 2	(2)
Portuguese West Africa (Angola)	25,000	25,000	25,000	25,000	(3)	(6)
Somaliland:			'	i .		1
British (exports)	950	353	(2)	(2)	(2) (3)	(2)
French (exports)	85, 273	(2)	(9)	1 6	۳	6
South-West Africa: Rock salt	669	641	751	1, 125	10 671	(3)
Other salt	3, 443		4,704	5, 364	10 3, 445	(2)

See footnotes at end of table.

# World production of salt, 1937-42, by countries, in metric tons-Continued

Country	1937	1938	1939	1940	1941	1942
Africa—Continued. Sudan, Anglo-Egyptian. Tanganyika Territory Tunisia. Uganda Union of South Africa	34, 553 8, 723 129, 708 3, 133 106, 338	37, 532 9, 678 129, 287 3, 169 117, 717	40, 633 9, 472 (2) 2, 626 (2)	40, 471 9, 505 (2) 3, 374 (2)	(2) (2) (2) (2) (3) (2)	(2) (2) (2) (2) (2)
Oceania: Australia: South Australia. Western Australia.	74, 739 3, 729	76, 013 3, 850	80, 759 (²)	146, 991 (²)	173, 431 (²)	(2)

<sup>In addition to the countries listed, salt is produced in Albania, Bolivia, Eritrea, Gold Coast, Leeward Islands, Madagascar, Southern Rhodesia, U. S. S. R., and Victoria (Australia), but figures of production are not available.

Juan not available.

Juanary to June, inclusive (Croatia only).

Stimated annual production.

Unoccupied China.

Juanuary to September, inclusive.

Year ended March 31 of year following that stated. Figures do not include output from salt beds which, although situated on government beach lands, have no fixed areas.</sup> 

Incomplete data.
 January to July, inclusive.
 January to June, inclusive.

# MAGNESIUM COMPOUNDS AND MISCELLANEOUS SALINES

By Charles L. Harness and Nan C. Jensen 1

## SUMMARY OUTLINE

	Page		Page
Summary Part I.—Magnesium compounds Magnesite. Salient statistics Prices. Review by States.	1491 1491 1491 1492 1494 1494	Part II.—Miscellaneous salines.  Calcium chloride Bromine.  Iodine. Sodium sulfates and carbonates. Borates.	1501 1501 1503 1504 1505 1507
Foreign countries Refractory magnesia from sources other than magnesite Dolomite Other magnesium compounds	1496 1497 1497 1499		

#### SUMMARY

War and essential civilian requirements absorbed nearly the entire output of the magnesia and natural-salines industries during 1942. Magnesia refractories were derived from magnesite, brucite, dolomite, sea water, and well brines principally to satisfy the increasing demands of open-hearth and electric steel furnaces. Caustic-calcined magnesite was used for flooring war plants and cargo ships. The total output of magnesium chloride from well brines, sea water, dolomite, and magnesite increased tremendously over production in previous years to meet magnesium-metal requirements. Consumption of calcium chloride grew in nearly all its customary uses, but particularly in freezeproofing coal and ores to facilitate unloading and release of cars. Bromine was valuable as a raw material in compounding antiknock fluids needed in mechanized warfare, and the production of iodine expanded. Sodium sulfates, carbonates, and borates were used increasingly to make glass containers, glass instruments, and structural glass—replacing metals needed for more vital war purposes.

# Part 1.—MAGNESIUM COMPOUNDS MAGNESITE

The expansion in output of basic open-hearth and electric furnace steel was probably the chief single factor in the record production of raw magnesite in 1942. Magnesite and magnesia from other sources as a whole did not become critical during 1942, although shortages developed in certain of the purer grades. On their own initiative, producers undertook allocation of the scarcer grades of calcined magnesite and magnesia from sea water.

 $<sup>^{\</sup>rm I}$  Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce,

# Salient statistics of the magnesite industry in the United States, 1938-42

발표 많은 사람들이 살아지고 먹다.	1938	1939	1940	1941	1942
Crude:					
Mined:			March 1990		
Short tons	1 97, 000	1 198, 980	1 333, 166	374, 799	1 497, 368
Value 1	\$725,000	\$1, 465, 190	\$2, 487, 969	\$2, 655, 547	\$3, 874, 334
Sold by producers:					
Short fonsValue	919	1, 123	2, 133	4, 536	6, 835
Value	\$12, 332	\$15, 752	\$32, 810	\$54,045	\$57, 350
Average per ton 2	\$13, 42	\$14.03	\$15.38	\$11.91	\$8.39
Imports for consumption:		*		Ψ-1.01	40,00
Short tons	36	569	22		
Short tons Value	\$777	\$5, 456	\$761		
Apparent new supplyshort tons	955	1,692	2, 155	4, 536	6, 835
Percent domestic	96. 2	66. 4	99. 0	100.0	100.0
Caustic calcined:					
Sold by producers:3					
Short tons	7. 400	10, 157	16, 261	30, 225	35, 485
ValueAverage per ton 2	\$228, 498	\$310, 102	\$512,607	\$1,052,077	\$1, 540, 573
Average per ton 2	\$30.88	\$30, 53	\$31, 52	\$34.81	\$43.41
	,,,,,,		402.02	401.01	ψ10. 11
Short tons	1, 452	2, 218	928	865	577
Value	\$39, 551	\$51, 884	\$21,301	\$23, 972	\$19, 105
	400,001	401,001	Ψ21, 001	Ψ20, 512	Ψ10, 100
Apparent new supplyshort tons	8, 852	12, 375	17, 189	31, 090	36, 062
Percent domestic	83. 6	82.1	94. 6	97. 2	98. 4
Refractory magnesia:					
Short tons	38, 738	86, 077	140, 668	201, 481	273, 661
Value	\$730, 978	\$1,699,723	\$2,802,537	\$5,052,879	\$7, 823, 963
Average per ton 2	\$18.87	\$19.75	\$19.92	\$25.08	\$28.59
Imports for consumption:	Ψ10.01	Ψ10.70	φ10.02	φ20.00	<b>Ф40.</b> 09
Short tons	24, 990	44, 420	30, 951	36, 792	7, 728
Short tonsValue	\$371, 669	\$800, 664	\$551, 536	\$824,068	\$280, 342
	45.1, 090	4000,001	4001, 000	4021,000	Ψ200, 012
Apparent new supplyshort tons	63, 728	130, 497	171, 619	238, 273	281, 389
Percent domestic	60.8	66.0	82.0	84.6	97.3

<sup>&</sup>lt;sup>1</sup> Partly estimated; most of the crude is processed by the mining companies, and very little enters open market.

<sup>2</sup> Average receipts f. o. b. mine shipping point.

<sup>3</sup> 1938-41: Includes caustic-calcined magnesite and caustic-calcined magnesia from sea-water bitterns; 1942: Includes caustic-calcined magnesite and caustic-calcined magnesia from sea-water bitterns, well brines, and

raw sea water.

4 1938-40: Includes dead-burned magnesite and refractory magnesia from sea-water bitterns; 1941: Includes dead-burned magnesite and refractory magnesia from brucite, dolomite, and sea-water bitterns; 1942: Includes dead-burned magnesite and refractory magnesia from brucite, dolomite, and sea-water bitterns; 1942: Includes dead-burned magnesite and refractory magnesia from brucite, dolomite, sea-water bitterns, well brines, and raw sea water.

Magnesium compounds sold or used by producers in the United States in 1942, by kinds and sources

[Quantities and values reported apply to finished products, not raw materials]

Finished products	From n	nagnesite	mite,	ucite, dolo- and sea- bitterns	From well brines, dry-lake brines, and raw sea water	
	Short tons	Value	Short tons	Value	Short tons	Value
Magnesia: Caustic-calcined	19, 551 189, 218	\$798, 019 4, 397, 766	}1 93, 521	1 \$3, 907, 396	2 7, 467	² \$497, 434
Total magnesia	208, 769	5, 195, 785	1 93, 521	1 3, 907, 396	2 7, 467	<sup>2</sup> 497, 434
Other magnesium compounds: Precipitated magnesium carbonate Magnesium chloride Calcium-magnesium chloride	(3) (3)	(3) (3)	59, 666 10, 847	5, 096, 231 262, 297	(3) 238, 499 (4)	(3) 7, 047, 917
Magnesium sulfate Magnesium hydroxide					40, 265 (³)	1, 029, 662
Undistributed 5	9, 796	337, 504			3, 819	464, 753
Total other magnesium compounds	9, 796	337, 504	70, 513	5, 358, 528	282, 583	8, 542, 332
Total all magnesium compounds.	218, 565	5, 533, 289	164, 034	9, 265, 924	290, 050	9, 039, 766

<sup>1</sup> Includes caustic-calcined and refractory magnesia and magnesia from precipitated carbonate.

<sup>2</sup> Includes caustic-calcined and refractory magnesia and magnesia from precipitated carbonate and from magnesium hydroxide.

<sup>3</sup> Included under "Undistributed."

<sup>4</sup> Reported in Calcium Chloride section of this chapter.

<sup>5</sup> Includes items entered as "(3)" above.

Sales of dead-burned magnesite increased in 1942, exceeding the 1941 record. Most of the output was consumed in construction and repair of basic open-hearth steel furnaces, though some of the purer material was used in brickmaking. Imports of dead-burned magnesite, normally totaling about 35,000 tons a year, mainly from Austria, Greece, and Manchuria, declined heavily in 1942. The foreign supply pattern changed considerably, the principal source being the An impending shortage of magnesite brick was avoided by increasing the use of periclase with chromite to form the "kromag" type of brick, said to be interchangeable with or even preferable to all-magnesite brick in certain parts of open-hearth steel furnaces.

The state of the s

Caustic-calcined magnesite showed widely diverse adaptability to the war program. It was used chiefly in oxychloride cements for sparkproof flooring for industrial plants and interior decking of ships. Fortunately, the lower and more abundant grades of caustic-calcined magnesite (82 to 84 percent MgO before ignition) were suitable for this purpose. Oxychloride floors are particularly valuable in explosive plants and aluminum-powder plants, as their electrical conductivity prevents accumulation of electrical charges in objects being moved over the floor, thus reducing the danger of static sparking. floors are also resistant to abrasive sparking.2

<sup>&</sup>lt;sup>2</sup> Chemical and Metallurgical Engineering, vol. 50, No. 1, January 1943, p. 83.

Magnesium metal was the next-largest direct outlet for caustic-calcined magnesite. Permanente Metals Corporation, Permanente, Calif., reduces its sea-water magnesia by the Hansgirg carbothermic process, whereas Basic Magnesium, Inc., chlorinates the calcined ore to anhydrous magnesium chloride for electrolytic reduction at Royson near Las Vegas, Nev. Substantial quantities of caustic-calcined magnesia were used as fertilizer, particularly in Florida. The synthetic-rubber industry employed high-grade magnesia derived from sea water as a catalyst and lower grades, including those obtained from magnesite, as fillers. Sea-water magnesia was also consumed in making rayon-coagulating solution. Other important uses of caustic-calcined magnesia were in fused refractory cements, glass insulators, boiler-water treatment, chemical reagents, and glue.

#### PRICES

The maximum price of \$22 a short ton for maintenance grade of domestic grain magnesite in bulk (add \$4 a ton for bags or sacks, carlots), f. o. b. Chewelah, Wash., established by Order 75 of the Office of Price Administration on January 28, 1942, continued in effect throughout the year. Owing to shortages of this grade of magnesite. however, the Westvaco Chlorine Products Corporation was permitted by the Office of Price Administration to sell dead-burned grain magnesite from its stocks at Patterson and Permanente, Calif., at \$32 a ton, f. o. b. Chewelah, Wash., to steel producers on the West coast, an equivalent of \$40.50 a ton f. o. b. Patterson and Permanente. The shortage was relieved early in the year, but the \$32 ceiling remained in nominal effect. From its Patterson (Calif.) plant, Westvaco Chlorine Products Corporation was permitted to sell dead-burned grain to the Vanadium Corporation of America and to the Mathieson Alkali Works (Inc.) at \$40.50 a ton. Early in 1943 the Westvaco Chlorine Products Corporation was permitted an increase of \$2.24 a short ton in brickmaking grades of magnesia shipped from Livermore. The 85-percent magnesia grade ceiling price, f. o. b. Livermore, was raised to \$38.24 a short ton and the 90-percent grade to \$38.74.

The following prices per ton were quoted for magnesia by the Westvaco Chlorine Products Corporation, in carlots f. o. b. California, during 1942: Caustic-calcined magnesite, bulk, \$52.75; powdered, \$58.75; calcined (sea-water) magnesia, bulk, \$54; powdered, \$60; mined periclase, bulk, 85 percent, \$38.24; 90 percent, \$38.74; seawater periclase, bulk, 85 percent, \$36.00; 90 percent, \$36.50.

#### REVIEW BY STATES

California.—Johns-Manville Products Corporation, Redwood City, prepared 85-percent magnesia insulation for steam pipes and boilers, using crude magnesite as a raw material. The Marine Magnesium Corporation continued to extract high-quality magnesia for medicinal and other purposes from raw sea water at San Francisco, using the

<sup>&</sup>lt;sup>3</sup> Tiger, H. L., Silica Removal [from boiler feed water] by Improved Magnesia Process: Trans. Am. Soc. Mech. Eng., vol. 64, 1942, pp. 49-63; Brit. Chem. and Phys. Abs., B, I, I, November 1942, p. 442.

and the second restriction of the second sec

Chesny process. The Permanente Metals Corporation began production of calcined magnesia from sea water at Moss Landing, Calif., for use in its carbothermic magnesium retorts; and its affiliate, the Permanente Cement Co., shipped magnesite from Luning, Nev., for calcining at its San Jose (Calif.) kiln. Plant Rubber & Asbestos Works, San Francisco, erected a new plant at Emeryville, Calif., to make 85-percent magnesia insulation from a sea-water-bittern derivative and continued production of magnesia insulation at its Redwood City (Calif.) plant, using sea-water bitterns. Westvaco Chlorine Products Corporation mined magnesite at its Bald Eagle mine near Gustine, Calif., and at its Western mine near Livermore, Calif. magnesite, together with that purchased from the properties of the Sierra Magnesite Co., Luning, Nev., was calcined in seven rotary kilns at Gustine, Livermore, Patterson, and Newark, Calif. Two of the Newark kilns also calcined magnesia derived from sea-water

Nevada.—Basic Magnesium, Inc., producing magnesium metal at Royson, Nev., near Las Vegas, mirred, concentrated, and calcined magnesite in 1942 at Toiyabe, Nev., north of the Luning magnesite area. The calcined material was shipped to Royson by truck and rail for chlorination and conversion to metal. The truck haul is 350 miles, but the rail route, which is quite indirect, is over 1,000 miles. Seeking to eliminate this costly rail haul and to assure an almost inexhaustible supply of magnesia, the Bureau of Mines conducted research on the recovery of magnesia from a 400,000,000-ton dolomite deposit at Sloan, 19 miles southwest of Las Vegas. The Bureau developed a process of leaching partly hydrated dolomite with magnesium chloride solution, whereby the calcium hydroxide is dissolved, leaving a magnesium hydroxide precipitate, which is filtered and calcined to magnesium oxide. The magnesium chloride needed for leaching is regenerated in a carbonation step, which simultaneously produces calcium carbonate. The two end products of the process are magnesium oxide and calcium carbonate. Bureau engineers have carried the project further by developing a method whereby the magnesia can be fed directly into the electrolytic cell.

Basic Magnesium, Inc., which is scheduled to produce eventually 112,000,000 pounds of magnesium metal annually, will require about

300 tons of magnesia daily when it attains full capacity.

Basic Refractories, Inc., Cleveland, Ohio, continued shipping brucite from the Luning area. The mineral is calcined at Maple Grove, Ohio, and is combined with stabilized dolomite to produce a grain-magnesia

refractory containing about 65 percent MgO.

The Sierra Magnesite Co., owned jointly by Westvaco Chlorine Products Corporation (Newark, Calif.) and Henry J. Kaiser and his associates (Oakland, Calif.), mined magnesite from the rich Segerstrom property and other claims near Luning, the crude mineral being shipped to Newark and San Jose, Calif., for calcining.

The Bureau of Mines has published data on occurrences of mag-

nesite and dolomite near Boulder Dam, Nev.4

<sup>4</sup> Schlocker, J., Magnesium-Bearing Minerals in the Boulder Dam Area for the Production of Magnesium Metal: Bureau of Mines Inf. Circ, 7216, 1942, 16 pp.

Texas.—Meramec Minerals Co., Hanna Bldg., Cleveland, Ohio, and C. E. Heinz of Llano, Tex., continued to produce magnesite in the

Llano County area.5

Washington.—The Northwest Magnesite Co., Farmers Bank Building, Pittsburgh, Pa., by far the largest producer of magnesite in 1942, operated the seven rotary kilns of its Chewelah (Wash.) plant at capacity during the year, producing mostly maintenancegrade magnesite for open-hearth furnaces but also shipping considerable brickmaking magnesite derived from the firm's new flotation The Washington State Department of Geology reported that the Turk mine in southwestern Stevens County contains two bodies of magnesite about 500 feet apart and estimated that the two bodies contain 500,000 tons of metallic magnesium.6

#### FOREIGN COUNTRIES

Information on foreign developments in magnesite has been meager since the outbreak of the war. • The latest Minerals Yearbook table showing world production by countries appeared in the volume reviewing 1939. During the 5-year period 1934-38, the U.S.S.R. produced about 534,000 short tons of crude magnesite annually, followed by Austria with 403,000 tons, Manchuria 233,000 tons, United States 157,000 tons, Greece 134,000 tons, and Czechoslovakia 83,000 tons.

Australia.—Magnesite obtained near Port Augusta, South Australia, is used in the new magnesium metal plant of the Broken Hill Pro-

prietary Co. at Newcastle.7

Bahamas.—The sea-water magnesia plant under construction at Inagua by West India Chemicals, Ltd., was not completed in 1942 owing to difficulty in obtaining equipment.

Brazil.—A large deposit of magnesite in Ceara, already producing on a small scale, is said to be capable of supplying 150 metric tons of

calcined magnesite monthly for export.8

Canada.—The Aluminum Co. of Canada, Ltd., erected a plant at Wakefield, Quebec, for the extraction of magnesia from brucitic limestone found in the area. Employing the process developed by Goudge, the company calcines the rock and adds enough water to hydrate the lime, which is then removed from the magnesia granules by air separation, washing, and screening. The magnesia is delivered to Canadian Refractories, Ltd., at Kilmer, Quebec, where it is made into refrac-In past years, Canadian Refractories, Ltd., tories and other products. and the International Magnesite Co., Ltd., have used as raw material for their basic refractories a magnesitic dolomite from Argenteuil

<sup>\*\*</sup>Chelf, Carl, Magnesite Mining in Llano County, Tex.: Mineral Resource Survey Circ. 40, University of Texas, Austin, Tex., 1941, 6 pp. See also McCammon, J. H., Report on Tin and Magnesite Deposits in Mason County, Tex.: Mineral Resource Survey Circ. 32, University of Texas, Austin, Tex., 1941, pp. 4-6.

\*\*Engineering and Mining Journal, vol. 144, No. 4, April 1943, p. 101.

\*\*Engineering and Mining Journal, vol. 143, No. 5, May 1942, p. 99.

\*\*Rock Products, vol. 45, No. 5, May 1942, p. 94.

Tyler, P. M., Industrial Minerals: Eng. and Min. Jour., vol. 144, No. 2, February 1943, p. 110.

Refractories Journal, vol. 19, No.1, January 1943, p. 18.

\*\*Goudge, M. F., A Preliminary Report on Brucite Deposits in Ontario and Quebec and Their Commercial Possibilities: Canadian Bureau of Mines Memorandum Ser. 75, 1939, 57 pp. Magnesia from Canadian Brucite: Trans. Canadian Inst. Min. and Met., vol. 43, 1940, pp. 481-505. Sources of Magnesia and Magnesium in Canada: Trans. Canadian Inst. Min. and Met., vol. 45, 1942, pp. 191-207.

County, Quebec. It is reported that the former firm acquired the holdings of the latter in 1942 and will continue to produce refractory and reactive magnesias.

Cuba.—Magnesite was mined by numerous small farmers near Santa Clara, where it was caustic-calcined for export, principally to the

United States.

Germany.—According to Mineral Trade Notes, 10 the Austrian and Bavarian magnesite companies have joined to form one large magnesite trust with headquarters in Berlin. The new company is styled

Südost-Magnesit Ges. and has a capital of 1,000,000 marks.

Union of South Africa.—Deposits and production were reviewed in The South African Mining and Engineering Journal.<sup>11</sup> Reserves are estimated at not over 260,000 tons of minable material, found mostly at Burgersfort, Kaapmuiden, and in the Sutherland Range. Production is limited to a few thousand tons a year.

Venezuela.—The deposits on the Island of Margarita are said to

contain over 6,000,000 tons of silica-free magnesite, and plans are

under way to reopen the mines.12

## REFRACTORY MAGNESIA FROM SOURCES OTHER THAN MAGNESITE

Particular shortages were felt in high-quality periclase for brickmaking, but production of periclase by new plants in 1943 from sea water, well brines, and dolomite is expected to relieve the deficit.

Greater use of rammed dolomite-base furnace linings eliminated considerable basic brick corbeling along the front, back, and end walls of the furnaces. It is claimed that dolomite-base linings, if over 15 inches thick, can safely be rammed directly on fireclay brick and that such a bottom can be installed in less than half the time required

to burn in an all-magnesite bottom, thus cutting fuel costs.

Recent developments in basic refractories were reviewed at the 25th conference of the Open-Hearth and Blast Furnace and Raw Materials Committees of the Iron and Steel Section of the American Institute of Mining and Metallurgical Engineers in April 1942 at Cincinnati. Rammed bottoms, in contradistinction to the older permanent hearth of bricks and working surface of magnesite, were shown to rebuild Bottoms of the stabilized dolomite-clinker or magnesiamuch faster. chromite types are rammed a section at a time to predetermined dimensions. A layer of grain magnesite or grain dolomite may be burned in on top of the permanent hearth to serve as the working hearth, though this addition is said to be unnecessary.

The Bureau of Mines published a summary of methods for producing

stabilized dolomite refractories.13

#### DOLOMITE

Shipments of dead-burned dolomite, stimulated by requirements of the steel industry, were 15 percent greater in quantity in 1942 than in 1941.

86-88.

<sup>13</sup> Schallis, Alvin, Dolomite-Base Refractories: Bureau of Mines Inf. Circ. 7227, 1942, 11 pp.

Bureau of Mines, Mineral Trade Notes: Confidential Series 3, September 1942, p. 26.
 South African Mining and Engineering Journal, vol. 53, pt. 2, No. 2595, October 24, 1942, pp. 167, 169,

<sup>171.</sup> 12 Engineering and Mining Journal, vol. 143, No. 6, June 1942, p. 104; vol. 143, No. 8, August 1942, pp.

Dead-burned dolomite sold in and imported into the United States, 1938-42

	Sales		Imp	Imports 1		Sa	Imports 1		
Year	Short tons	Value	Short tons	Value	Year	Short tons	Value	Short tons	Value
1938 1939 1940	366, 626 671, 561 867, 909	\$3, 095, 355 5, 447, 554 6, 925, 328	2, 875 186	\$67, 340 4, 260	1941 1942	1, 069, 887 1, 229, 357	\$9, 111, 172 10, 817, 634	449	\$11, 260

<sup>1</sup> Reported as' 'dead-burned basic refractory material."

Dolomite has long been used as a basic refractory for open-hearth maintenance and repair, averaging five to eight times the quantity of magnesite used for refractory purposes. Only recently, however, has dolomite invaded the metal field, competing with and supplementing magnesite and brines as a source of magnesium metal and compounds.

The following outline covers methods of recovering magnesium from dolomite which were either in commercial use during 1942 or to be

used in plants under construction in that year.

1. Direct reduction with ferrosilicon to magnesium metal. This process is used by New England Lime Co., Canaan, Conn.; Ford Motor Co., Dearborn, Mich.; Electro-Metallurgical Co., Spokane, Wash.; Amco Magnesium Co., Wingdale, N. Y.; Magnesium Reduction Co., Luckey, Ohio; and Permanente Metals Cor-

poration, Manteca, Calif.

2. Processes based upon the reaction  $Ca(OH)_2 + Mg(OH)_2 + MgCl_2 \rightarrow CaCl_2 + 2Mg(OH)_2$ . The calcium and magnesium hydroxides are obtained by slaking calcined dolomite, and the magnesium chloride is a constituent of sea water and well brines. Calcium chloride may be added to well brines and sea-water bitterns before the milk of dolomite is added, in order to precipitate sulfate ions as synthetic gypsum (calcium sulfate), which is sold as a byproduct. If this preliminary step is not used, synthetic gypsum is precipitated to some extent with the magnesium hydroxide. The precaution is unnecessary with raw sea water, as the solution of salts is so dilute that any gypsum formed is redissolved. Permanente Metals Corporation (plant at Moss Landing, Calif.) and Northwest Magnesite Co. (plant at Cape May, N. J.) use the process to recover magnesia from raw sea water, the former for conversion to metal and the latter for refractory use; and The Dow Chemical Co. at Ludington, Mich. (plant not completed in 1942), and the Michigan Chemical Corporation, St. Louis, Mich., use (or will use) the method with well brines as the raw material, the former for metal use and the latter for refractory purposes.

latter for refractory purposes.

3. Processes based upon the reaction, Ca(OH)₂+Mg(OH)₂+CaCl₂+2CO₂ → MgCl₂+2CaCO₃+2H₂O. The calcium and magnesium hydroxides are obtained by hydrating calcined dolomite, and in present practice the calcium chloride used is a byproduct of the Solvay soda ash process. Carbon dioxide is available from the dolomite kiln gases. There are several possible variations in the process, depending on whether the end product desired is magnesium chloride or magnesium hydroxide and also on the purity and grain size of the dolomite. If the dolomite is too fine-grained it may be impracticable to recover the magnesium content as magnesium hydroxide, for the latter becomes more gelatinous and progressively harder to filter with decreasing dolomite grain size. The process is employed by the Diamond Alkali Co., Painesville, Ohio; Mathieson Alkali Works (Inc.), Lake Charles, La.; and in a pilot plant of the Bureau of Mines at

Boulder City, Nev., all for conversion to metal.

4. Dolomite is calcined and washed with carbon dioxide-free water, which dissolves most of the lime, leaving magnesia undissolved. The Standard Lime & Stone Co. uses the process at its Millville, W. Va., plant, making "Sta-set" magnesia-grain refractories.

5. Milk of dolomite is carbonated, precipitating calcium carbonate, which is

removed, leaving magnesium bicarbonate in solution.

removed, leaving magnesium of carbonate in solution.

(a) The solution is then heated, precipitating a basic magnesium carbonate. This is the Pattinson process used by Philip Carey at Plymouth Meeting, Pa.; Ehret Magnesia Manufacturing Co., Valley Forge, Pa.; Johns-Manville Products Corporation, Manville, N. J., and Waukegan, Ill.; Keasbey & Mattison Co., Ambler, Pa.; and Standard Lime & Stone Co., Millville, W. Va. Basic magnesium carbonate is used in making "85-percent magnesia" insulation for steam

boilers and pipes.

(b) The solution is neutralized with hydrochloric acid, yielding magnesium chloride. This process is to be used by the International Minerals & Chemical chloride.

Corporation, Austin, Tex., supplementing its supply of byproduct magnesium chloride from Carlsbad (N. Mex.) potash brines for conversion to metal.

6. Milk of dolomite is reacted with hydrogen sulfide, thereby dissolving the calcium as calcium bisulfide and leaving a precipitate of magnesium hydroxide, which may be filtered and calcined. The method is used by the Warner Co.,

chapter of this volume.

Devault, Pa., for making refractory magnesia.

7. Milk of dolomite is used instead of lime in the ammonia kilns in the 1. MILK OI GOIOMITE IS used instead of time in the ammona kills in the ammonia-soda process; ammonia is driven off, leaving magnesium hydroxide and magnesium oxide in a solution of calcium chloride. The insoluble magnesium compounds are filtered off and reacted with hydrochloric acid to yield magnesium chloride for conversion to metal. The hydrochloric acid is a byproduct of the magnesium metal cell. This so-called "acid process" is one used by the Diamond Alkali Co.

In 1942 the Bureau of Mines compiled a list of occurrences and analyses of domestic high-grade dolomite.14

THE PARTY OF THE P

Other aspects of the dolomite industry are reviewed in the Stone

# OTHER MAGNESIUM COMPOUNDS

The production of precipitated magnesium carbonate, magnesium chloride, magnesium sulfate, and magnesium hydroxide from magnesite, dolomite, sea-water bitterns, raw sea water, well brines, and dry-lake brines in 1942 was reported to the Bureau of Mines as 362,892 short tons valued at \$14,238,364, compared with 103,906 tons valued Part of the increase in the 1942 figure is due at \$3,288,687 in 1941. to general expansion in output of virtually all magnesium compounds, especially magnesium chloride, and part to the inclusion in 1942 data of precipitated magnesium carbonate from dolomite, which was not included in the 1941 figures. In neither year do the figures include the magnesium sulfate derived from magnesite.

<sup>14</sup> Weitz, J. H., High-Grade Dolomite Deposits in the United States: Bureau of Mines Inf. Circ. 7226,

The production of all natural magnesium compounds, including those obtained from saline deposits or derived from natural brines, and including brucite but not including magnesite or dolomite or their derivatives, amounted to 369,257 short tons in 1942, valued at \$10,727,560. The figures (137,357 tons valued at \$3,587,784) given for 1941 in Minerals Yearbook, 1941, are not strictly comparable with those for 1942, as they do not include the production of magnesia from sea-water bitterns.

Expansion in magnesium chloride production for reduction to magnesium metal was the chief feature of the magnesium salines industry in 1942. The Dow Magnesium Corporation produced magnesium hydroxide from sea water at its new Velasco (Tex.) plant, finished in 1942. The magnesium hydroxide is converted to chloride and electrolyzed to magnesium metal. The same process is used in the nearby Freeport (Tex.) plant of The Dow Chemical Co. At Midland, Mich., The Dow Chemical Co. recovered magnesium chloride from well brines for use in making metal.

brines for use in making metal.

The Arizona Chemical Co. extracted magnesium sulfate (calcined) from well brines at O'Donnell, Tex. The C. A. Kearney Co. pumped magnesium sulfate-bearing brines from Epso Lake near Tonasket, Wash., and crystallized Epsom salt from the liquors. The Morton Salt Co. precipitated magnesium carbonate from well brines at its Manistee (Mich.) plant. The Ozark Chemical Co., of Tulsa, Okla., drilled wells into a magnesium chloride deposit near Gail, Borden County, Tex., and investigated methods of recovering commercial products from the brine.

Research into the extraction of magnesium salts from readily available magnesium silicate rocks continued in 1942. Olivine Products, Inc., Sylva, N. C., for several years a producer of Epsom salt from olivine and sulfuric acid, was inactive during the year, but the International Minerals & Chemical Corporation erected a plant at Augusta, Ga., to recover Epsom salt from serpentine. According to reports received by the Bureau of Mines, production was to begin early in 1943.

The Bureau of Mines, cooperating with the Geological Survey as agents for the Defense Plant Corporation, core-drilled into magnesium-bearing strata on the lease of the Utah Magnesium Corporation near Thompson, Grand County, Utah, in 1942. A very rich section of carnallite (KMgCl<sub>3</sub>.6H<sub>2</sub>O) and sylvite (KCl), 220 feet thick, was cored at a depth of about 3,500 feet—the only magnesium-bearing section in the well. The lateral extent of the deposit is unknown, but it was estimated that the well cores prove 20 acres, with possibilities of a much larger area.

<sup>18</sup> Bureau of Mines, Thompson Magnesium Well, Utah: War Minerals Report 12, 1942, 39 pp.

# Magnesium compounds imported for consumption in the United States, 1938-42

Year	Magnesium chlo- ride (anhydrous and n. s. p. f.)		Magnesium sulfate (Epsom salts)		Calcined magnesi- um sulfate or cal- cined kieserite (not fertilizer)		al- Oxide ite m		
	Shorttons	Value	Short tons	Value	Short	tons	Valu	e Short to	ns Value
1938	28 (1) 28 186	\$1, 572 960 21 1, 328 115, 025	799 198 6 1	\$12, 328 3, 641 898 179		193 472	\$66, 4 43, 4	135 3 1	6 \$15,947 8 14,755 8 5,672 2 4,292 6 5,487
Year		Magnesium carbonate, precipitated			Manufactures of car- bonate of magnesia		Magnesium salts and compounds, n. s. p. f.2		
		Short tons	Value	Short	tons	Val	lue	Short tons	Value
1938		470 776 754 1,106 640	68, 934 82, 764 113, 236	1	3		\$209	48 59 92 23 13	\$17, 146 26, 788 44, 492 11, 488 6, 701

#### Part II.—MISCELLANEOUS SALINES

#### CALCIUM CHLORIDE

Shipments of calcium chloride and calcium-magnesium chloride from natural sources were 35 percent greater in quantity in 1942 than in 1941. However, total consumption of natural and synthetic calcium chloride is not believed to have increased significantly in 1942. The increased shipments of the natural material are said to have resulted from the shut-down of a former producer of synthetic calcium There were 13 producers of natural calcium and calciummagnesium chlorides in 1942, compared with 10 in 1941.

Calcium chloride and calcium-magnesium chloride from natural brines sold by producers in the United States, 1938-42

[In terms of 75 percent (Ca, Mg) Cl<sub>2</sub>]

Year	Short tons	Value	Year	Short tons	Value
1938 1939 1940	96, 470 108, 441 99, 536	\$1, 218, 938 1, 307, 717 998, 241	1941 1942	165, 932 224, 527	\$1, 333, 370 1, 733, 169

<sup>&</sup>lt;sup>1</sup> 109 pounds. <sup>2</sup> Magnesjum silicofluoride or fluosilicate included under "Magnesium salts and compounds, n. s. p.

Calcium chloride imported for consumption in and exported from the United States, 1938-42

Year	Jmr	orts	Exports		
Ivar	Short tons	Value	Short tons	Value	
1938	1, 642	\$21, 174	24, 118	\$396, 981	
1939 1940	996	12, 314	19, 382 8, 907	318, 199 194, 738	
1941 1942	7 1, 443	795 18, 926	20, 777 8, 336	511, 366 223, 184	
	1,110	10, 320	3,000	220, 104	

Calcium chloride and calcium-magnesium chloride recovered from natural brines are largely byproducts of the manufacture of bromine, sodium chloride, magnesium chloride, and certain other salts. Most of the calcium chloride produced in the United States is a byproduct of soda ash manufactured by the ammonia-soda process, and its cost is borne by the soda ash; in this synthetic calcium chloride, the calcium comes from limestone and the chlorine from salt. The output is not canvassed by the Bureau of Mines, but it is estimated that 4,000,000 tons of synthetic calcium chloride in solution were available as a byproduct of the ammonia-soda process in 1942, of which it is estimated 175,000 tons (185,000 tons in 1941) were recovered and sold, competing directly with calcium chloride from natural brines. Producers estimate that approximately 90 percent of the total natural and synthetic calcium chloride available from all sources is thrown away.

The following firms reported production of calcium chloride and calcium-magnesium chloride from natural brines in 1942: California Rock Salt Co., 2436 Hunter Street, Los Angeles, Calif., plant at Amboy, Calif.; J. Q. Dickinson & Co., Malden, W. Va.; The Dow Chemical Co., Midland, Mich.; Great Lakes Chemical Corporation, Filer City, Mich.; Hill Brothers Chemical Co., 2159 Bay Street, Los Angeles, Calif., plant at Amboy, Calif.; Liverpool Salt Co., Hartford, W. Va.; Michigan Chemical Corporation, St. Louis, Mich.; Mullet Island Salt Works, Niland, Calif.; Ohio River Salt Corporation, Mason W. Va.; Pomeroy Salt Corporation, Pomeroy, Ohio, plant at Minersville, Ohio; Rademaker Chemical Corporation, Eastlake, Mich.; and Westvaco Chlorine Products Corporation, 405 Lexington Avenue, New York, N. Y., plants at Chula Vista, Calif., and South Charleston, W. Va.

Calcium chloride is used chiefly in road stabilization, which accounts for nearly half the consumption. It is used also in the treatment of coal, air conditioning, preventing evaporation and freezing of water in fire buckets, and as a desiccator in oil pipe lines. A new commercial use is in the recovery of lithium chloride from spodumene concentrates. The process, which was developed by the Bureau of Mines, 16 involves heating spodumene with calcium chloride at high

<sup>&</sup>lt;sup>16</sup> Fraas, F., and Ralston, O. C., Chloride Volatilization of Lithium from Spodumene: Bureau of Mines Rept. of Investigations 3344, 1937, 11 pp.

temperature, whereby the lithium is volatilized as the chloride and recovered. Other important outlets for solid calcium chloride or its solutions are in freezeproofing coal and various ores, in removing ice on streets and highways, in brines at refrigerating plants, in curing concrete, and in calcium-soap lubricants. A comparatively new household use is in dehumidification of basements and cellars; kits for this purpose are available in many department stores.

Prices of calcium chloride, flake, 77 to 80 percent, carlots, delivered,

Prices of calcium chloride, flake, 77 to 80 percent, carlots, delivered, ranged from \$18.50 to \$35.00 a ton throughout 1942, according to Oil, Paint and Drug Reporter. Solid calcium chloride, 73 to 75 percent, was quoted at \$18.00 to \$34.50 a ton, carlots, delivered; and 40-

percent solutions, \$7.50 a ton, tanks, works.

#### BROMINE

A CONTRACTOR OF THE PROPERTY O

一年 大學 一种一种一种一种一种一种一种一种一种一种

Shortage of gasoline for civilian use in 1942 was largely responsible for a 4-percent decrease from 1941 in output of bromine and its compounds, as bromine is a constituent of ethylene dibromide used in antiknock fluids. Nevertheless, heavy requirements for antiknock fluids for mechanized warfare maintained the total output of bromine at a relatively high level.

Bromine and bromine in compounds sold or used by producers in the United States, 1938-42

/ Year	Pounds	Value	Year	Pounds.	Value
1938 1939 1940	33, 324, 116 37, 882, 005 59, 266, 275	\$6, 610, 056 7, 611, 400 11, 772, 515	1941 1942	68, 317, 019 65, 880, 935	\$11, 506, 213 13, 729, 383

Fourteen plants produced bromine and its compounds in 1942, as follows: American Potash & Chemical Corporation, Trona, Calif.; J. Q. Dickinson & Co., Malden, W. Va.; The Dow Chemical Co., Midland, Mich.; Ethyl-Dow Chemical Co., Wilmington, N. C., and Freeport, Tex.; Great Lakes Chemical Corporation, Filer City, Mich.; Liverpool Salt Co., Hartford, W. Va.; Michigan Chemical Corporation, St. Louis, Mich.; Morton Salt Co., Manistee, Mich.; Pomeroy Salt Corporation, Minersville, Ohio; Rademaker Chemical Corporation, Eastlake, Mich.; and Westvaco Chlorine Products Corporation, South Charleston, W. Va., and Chula Vista and Newark, Calif. Most of it was produced by the Ethyl-Dow Chemical Co. at Wilmington, N. C., and Freeport, Tex., from raw sea water, and by The Dow Chemical Co. from well brines at Midland, Mich. Other raw materials used were sea-water bitterns and dry-lake brines.

An increasingly important use of bromine is in the preparation of methyl bromide, a fumigant for growing plants and stored grains. Bromine and bromides are also used in making tear gases, dyes, medicinals, photographic reagents, and certain kinds of synthetic

rubber.

Most bromine enters the market as ethylene dibromide, which was quoted over a range of 65 to 70 cents a pound in 60-pound drums during 1942, f. o. b. plant. Sodium and potassium bromides, U. S. P., granular, were quoted at 27 to 31 cents in 500-pound barrels, works; ammonium bromide at 31 to 35 cents; and bottled elemental bromine in cases at 25 to 30 cents a pound.

#### IODINE

There was no problem in iodine procurement in 1942, due to ample domestic production and to large stocks of Chilean iodine—estimated at a year's supply—held in the United States by the Chilean Nitrate Sales Corporation, New York City. Although some iodine was recovered on the West coast from kelp during the first World War, the American iodine industry really was born in 1928, when The Dow Chemical Co. undertook to recover iodine from oil-well waste waters near Shreveport, La. Dow later transferred its operations to Venice and Seal Beach, Calif., again using oil-well brines, and the Louisiana plant was shut down. The Deepwater Chemical Co., Ltd., Compton, Calif., also produces iodine from oil-well wastes. As there have been only two producers since 1937, the Bureau of Mines is not at liberty to reveal domestic output. In 1937, domestic producers shipped 299,286 pounds valued at \$242,422. Production has been considerably higher in recent years.

Iodine is used in medicinals, photography, stock feed and human food, in organic syntheses, analytical reagents, leather manufacture,

and special soaps.

American output is very effective in keeping the price of Chilean iodine low. As late as 1931, Chilean crude iodine sold in the United States at \$4 a pound; in 1936 the price dropped to \$0.90 but has gradually risen since then to \$1.35 a pound less 5 percent, in 150-pound kegs, which price was constant throughout 1942. Resublimed iodine in 5-pound bottles, 50-pound lots, sold at \$2 a pound during the year.

Imports of crude iodine, all from Chile, were 951,243 pounds valued at \$1,051,432 in 1942, compared with 1,010,039 pounds valued at \$1,121,513 in 1941. War Production Board General Import Order of December 17, 1942, prohibited import and export of iodine except

by authorized persons.

Crude iodine imported for consumption in the United States, 1938-42

Year	Pounds	Value	Year	Pounds	Value
1938	570, 532 200, 000 1, 244, 146	\$464, 303 168, 238 1, 296, 181	1941 1942	1, 010, 039 951, 243	\$1, 121, 513 1, 051, 432

#### SODIUM SULFATES AND CARBONATES

Sales of natural sodium sulfates and carbonates increased 11 and 3 percent, respectively, in quantity in 1942 compared with 1941. Nine producers reported sales of natural sodium sulfate in 1942; eight reported for 1941. Natural sodium sulfate production rivals the output of salt cake and chemical sodium sulfates in the United States. Production of natural sodium carbonates, however, is small as compared with the quantity manufactured by the Solvay process, which yielded 3,944,000 short tons in 1942, according to Chemical and Metallurgical Engineering (vol. 50, No. 2, February 1943, p. 105). As in past years, nearly all the output of natural sodium carbonate was produced by four firms from Searles and Owens Lakes in California. In addition, a small quantity of soda ash was recovered from well brines in the vicinity of Green River, Wyo., which area is underlain by extensive strata of trona.<sup>17</sup>

It has been proposed for several years to recover potassium carbonate by reacting Green River trona with potassium-bearing wyomingite, also found near Green River, and in 1942 the Bureau of Mines erected a pilot plant to study the reaction. Potassium carbonate is used in the glass, ceramics, and chemical industries.

Natural sodium sulfates and sodium carbonates sold or used by producers in the United States, 1935-42

Year	Sodium s	ulfates 1	Sodium carbonates 2		
	Short tons	Value	Short tons	Value	
1935	38, 706 51, 608 80, 053	\$275, 943 336, 559 599, 266	93, 230 102, 866 104, 711	\$1, 173, 003 1, 106, 364 1, 191, 485	
1937 1938 1939	80, 210 137, 479 187, 233	596, 812 1, 027, 876 1, 528, 633	100, 010 124, 743 130, 034	1, 235, 328 1, 528, 810 1, 629, 283	
1940	157, 524 175, 033	1, 328, 033 1, 443, 137 1, 669, 983	146, 677 150, 619	1, 822, 986 2, 145, 289	

<sup>1 1935–38:</sup> Salt cake and Glauber's salt; 1939–42: Salt cake, Glauber's salt, and burkeite. 2 1935–41: Soda ash, bicarbonate, and trona; 1942: Soda ash and trona.

The American Potash & Chemical Corporation (plant at Trona, Calif., on Searles Lake) rushed the expansion of its Soda Products Plant during 1942; the new units were expected to be in operation early in 1943. As a raw material for some of its soda ash and salt cake, the expanded plant will use burkeite, a sodium carbonate-sulfate hitherto sold to the kraft-paper industry as a substitute for salt cake. The American Sulphates Co., Mecca, Calif., a new producer, extracted sodium sulfate from magnesium-sodium salts mined near Bertram, Imperial County, Calif. The deposit has been described by Sampson

<sup>17</sup> For a description of the deposit, see Smith, H. I., Trona in Wyoming: Am. Inst. Min. and Met. Eng. Tech. Pub. 1489, July 1942, 3 pp.
18 Ralston, O. C., and Stern, A. George, Annual Report of the Nonmetals Division, Fiscal Year 1942: Bureau of Mines Rept. of Investigations 3675, November 1942, p. 11.

and Tucker. 19 The Arizona Chemical Co., 30 Rockefeller Plaza, New York City, increased its output of sodium sulfate from well brines near O'Donnell and Brownfield, Tex. The Desert Chemical Co., 4031 Goodwin Avenue, Los Angeles, Calif., extracted sodium sulfate and sodium chloride from well brines at its Dale Lake plant near Twentynine Palms, Calif. The company enlarged its facilities and drilled additional wells in 1942 with the intent of increasing its capacity to 50,000 tons of sodium sulfate and 80,000 tons of sodium chloride annually. The Iowa Soda Products Co., Council Bluffs, Iowa, mined sodium sulfate from an open pit near Rawlins, Wyo., and operated the Rawlins refinery at capacity during the year, producing Glauber's salt for mineral feed and veterinarian requirements. The Natural Soda Products Co., 405 Montgomery Street, San Francisco, recovered sodium carbonate at Keeler, Calif., from Owens Lake, Invo County, for use mainly in glass, sodium chemicals, paper, and nonferrous metallurgy. The Ozark Chemical Co., Mid-Continent Building, Tulsa, Okla., operated its Monahans (Tex.) plant at full capacity during 1942, recovering sodium sulfate from well brines. The major portion of the output was of "salt-cake" grade and was shipped to kraft pulp mills; the remainder was consumed by the glass and chemical industries. The Pacific Alkali Co., 523 West Sixth Street, Los Angeles (plant at Bartlett, Calif.), extracted soda ash and trona from Owens Lake brines for use in mining and metallurgy, cleansers, and glass. W. E. Pratt, Casper, Wyo., mined sodium sulfate near Casper and converted it to Glauber's salt. The Washington Chemical & Salt Corporation, Brewster, Wash., in a test run extracted about 20 tons of sodium sulfate from a dry lake near Monse, Wash. The West End Chemical Co., 608 Latham Square Building, Oakland, Calif., increased its production of sodium carbonate from Searles Lake and began the construction of additions to its plant, including carbonating towers, tanks, and other facilities, the cost of which is estimated at \$300,000.

The uses of natural and synthetic sodium sulfate are approximately the same; both are used in the manufacture of kraft pulp; flat, pressed, fiber, and optical glass; antimony recovery; stock feeds; dye standardization; and control of caustic embrittlement of boilers. The use of

sodium sulfate in glassmaking was reviewed by Weyl.<sup>20</sup>

The chief use of natural sodium carbonates is in glass (mostly container), which takes nearly half the output. Large quantities of trona, Na<sub>2</sub>CO<sub>3</sub>.NaHCO<sub>3</sub>.2H<sub>2</sub>O, and hydrated sodium carbonate are consumed in cleansers. Increasing quantities of natural sodium carbonate are being used in the metallurgy of tungsten, molybdenum, vanadium, and antimony.

In 1942 the Bureau of Mines published a brief analysis of the production and uses of sodium carbonate.<sup>21</sup> The second edition of Manufacture of Soda, by T. P. Hou, was published by the Reinhold

Publishing Corporation, New York City, in 1942.

Sampson, R. J., and Tucker, W. B., Mineral Resources of Imperial County: California Jour. Mines and Geol., vol. 38, No. 2, April 1942, pp. 140-143.
 Weyl, W. A., The Role of Sodium Sulfate in Glass Manufacture: Glass Ind., vol. 24, No. 1, January 1943, pp. 17-20, 39.
 Harness, C. L., and Coons, A. T., Sodium Carbonate: Bureau of Mines Inf. Circ. 7212, 1942, 35 pp.

Domestic salt cake was quoted at \$15 a short ton, bulk, works; anhvdrous sodium sulfate at \$1.70 to \$1.90 per hundredweight, works; and Glauber's salt at \$1.05 to \$1.28 per hundredweight throughout 1942, according to Oil, Paint and Drug Reporter. Soda ash, calcined sodium carbonate, was sold in 1942 at \$0.90 to \$3.25 a hundredweight, depending on grade and other factors.

#### BORATES

Boron-mineral production in 1942 slumped from lack of shipping space for exports and from shifts in the domestic consumption pattern. Shipments of boron minerals and boron derivatives made by the producers of boron minerals were 25 percent below those of 1941 in quantity. Five producers—all in California and same five that produced in 1941—reported shipments.

The state of the s

Salient statistics of the boron-mineral industry in the United States, 1938-42

	1938	1939	1940	1941	1942
Sold or used by producers: 1 '					
Short tons	215, 662	245, 284	243, 355	301, 282	226, 723
Value	\$4,739,291	\$5, 689, 797	\$5, 643, 390	2 \$6, 785, 662	\$5, 733, 648
Imports for consumption (refined): 3					
Pounds	631	3 774	752	2,025	
Value	\$131	* \$170	\$185	\$92	
Exports:		100	ľ		Burto Compa
Short tons	77, 519	91, 139	64, 313	41, 793	36, 542
Value	\$2,642,446	\$3, 230, 304	\$2, 456, 523	\$1,893,500	\$1, 562, 794
Apparent consumption: 4 Short tons	138, 143	154, 145	179, 042	259, 490	190, 181

<sup>1 1938:</sup> Borax, kernite, and boric acid; 1939: Borax, colemanite, kernite, ulexite, and boric acid; 1940-41: Borax, kernite, boric acid, and colemanite; 1942: Borax, anhydrous sodium tetraborate, kernite, boric acid, and colemanite.

<sup>2</sup> Revised figures.

The American Potash & Chemical Corporation, 122 East Fortysecond Street, New York City, extracted borax from the brines of Searles Lake at its Trona, Calif., plant and sold borax, dehydrated borax, and boric acid for domestic and foreign consumption in a wide variety of uses, but particularly in special glassware. The Pacific Alkali Co., 523 West Sixth Street, Los Angeles, recovered borax from Owens Lake, at Bartlett, Calif., chiefly for export. The Pacific Coast Borax Co., 510 West Sixth Street, Los Angeles, oldest and one of the largest producers, operated its kernite mines at Boron, Calif., and its Wilmington (Calif.) refinery (making kernite concentrates, borax, boric acid, and other boron derivatives) at near-capacity levels in 1942 for domestic and export trade. The United States Borax Co., 510 West Sixth Street, Los Angeles, mined colemanite (crude calcium borate) near Shoshone, Inyo County, Calif., for conversion into borax at a nearby refinery. The West End Chemical Co., 608 Latham Square Building, Oakland, Calif., recovered borax from Searles Lake at its Westend (Calif.) plant and sold both borax and dehydrated borax.

Also 348 pounds of crude valued at \$7 in 1939.

4 Quantity sold or used by producers plus imports minus exports.

Before the war, borax was used chiefly in porcelain enameling. Owing to the lack of steel for making stoves, refrigerators, and similar articles, the amount of borax consumed in the enameling industry was small in 1942. The major wartime use is in glass, principally container and bottle glass, and kitchen utensils (replacing aluminum, stainless steel, and enamelware). Borax in the glass batch enables glass to withstand, with minimum breakage, such treatments as washing and pasteurizing; borax improves the tensile strength, elasticity, and hardness of glass, thus facilitating handling and shipping. The salt is used in many types of optical glass, in heat-resistant laboratory ware, in reflectors and beacons for airports, in water-gage glasses, in the bulbs of electron tubes, and in "foamglas" insulation.

Boron minerals and their derivatives are also used in the manufacture of pharmaceuticals, in water treatment (pH control), in making detergents, in textile treatment, in alloy steels,22 as a preservative in adhesives, in rust inhibitors, and in abrasives. A molding sand for magnesium castings, containing boric acid to prevent reaction of magnesium with the moisture in the sand, has been described.23 The use of borax in fire-retardant paints is discussed in Technical Notes 249 of the Forest Products Laboratory, Madison, Wis. Borax con--tents of 32 to 50 percent of the total paint are typical. A steel producer reported that kernite (crude Na<sub>2</sub>B<sub>4</sub>O<sub>7</sub>·4H<sub>2</sub>O) could be substituted for aluminum as a scavenger in the ladle, on open-pour steels containing 0.10 percent carbon and under, accomplishing a saving of about 2.5 ounces of aluminum per ton of ingots without sacrificing quality.24 The use of borax as a plant food is growing. Application of 10 to 20 pounds of borax per acre to boron-deficient soils is said to stimulate the growth of alfalfa, vetch, turnips, beets, and other plants. Many of the more important articles dealing with this use are reprinted in "Boron-O-Gram," a bimonthly published by the Pacific Coast Borax Co., 510 West Sixth Street, Los Angeles, Calif.

The price of technical borax, granular, bulk, works, remained at \$41.50 a short ton throughout 1942, according to Engineering and

Mining Journal Metal and Mineral Markets.

<sup>22</sup> Tisdale, N. F., The Use of Boron in Steel and Iron: The Frontier, vol. 5, No. 4, December 1942, pp. 6-7, published by Armour Research Foundation, Chicago, Ill.

23 Metal Progress, vol. 4, No. 4, April 1942, p. 493.

24 Iron Age, vol. 149, No. 17, April 3, 1942, p. 53.

## **GEM STONES**

By SYDNEY H. BALL

## SUMMARY OUTLINE

	Page		Page
Jewelry industry in 1942	1509	Diamond	1515
Fashions in jewels	1510	Share dealings	1515
Domestic production	1510	Market	1515
Canada gem stones	1512	Imports	1515
Imports	. 1513	Cutting	1516
Metal shortages in American jewelry trade	1513	World production	1516
Price ceilings	1513		1517
Conversion of the jewelry industry	. 1514	Ruby, sapphire, emerald	1518
Government regulations	. 1514	Lesser gems	1519
Effect of war on the gem-stone trade	1514	Instrument and chronometer jewels	1519
		Bibliography	1520

#### **JEWELRY INDUSTRY IN 1942**

Retail sales by jewelry stores in the United States totaled \$699,000,000 in 1942—an all-time record and a 32.9 percent increase over 1941. Gains were particularly large in Washington and Oregon and in other areas where there are big war plants. As in the past 2 years, the increase was due to a large turn-over of relatively inexpensive items, although a few high-priced items were sold. Even the New York Fifth Avenue shops are showing more reasonably priced articles. The Christmas trade reached an all-time record, many believing it to be the last Christmas until the war is over when one could buy what one liked.

Increased sales were due to the marked rise in income of a large number of Americans (national income: 1939, 70 billion dollars; 1942, 119.8 billion dollars—thanks, unfortunately, to the war), to some investment buying, and to an all-time high in number of weddings (about 1,800,000 marriages, an 11-percent increase over 1941). Women war workers form a new class of jewelry-store customers, and some new fortunes are being made which will mean new purchasers

of gems.

National income in 1943 will be even greater than that in 1942; and, notwithstanding the markedly higher taxes, the public will be ready to buy jewelry, particularly that moderately priced. Retailers will have difficulty in keeping their showcases filled, even though their business, as is likely, may average less than that of 1942. However, they can get diamond-set palladium jewelry and other gem stones, probably set in gold, and will find dealing in old jewelry profitable. As retailers face a shortage in help and higher operating costs and taxes, as well as ceiling prices on their wares, their 1943 profits are not likely to be as large as those of 1942.

Sales by wholesalers showed smaller gains (9 percent), and yet their stocks decreased (10 percent). Retailers' stocks decreased during the

year, and certain lines (watches, alarm clocks, etc.) were sold out during the Christmas season; they are begging wholesalers for goods, and of course, owing to Government regulations, the situation will become more acute. Late in 1942 the War Production Board limited the size of inventories that might be carried by the large and financially more stable companies in the hope that stocks might be distributed more evenly among retailers. Inventories in 1942 shrank only slightly.

As far as selective service is concerned, the jewelry trade is to receive few favors; jewelry artisans, lapidaries, and salesmen (both

retail and wholesale) are nondeferrable.

Canadian retail sales were excellent before the new 25-percent excise tax was effective, June 23, 1942.

## FASHIONS IN JEWELS

The rather severe modern gown requires the gaiety of jewels. Utilitarian, though smart, jewelry characterized the mode in 1942, and hence multiple-use clips and other double-duty jewelry were popular. The vogue for gold continued to grow at the expense of platinum, which cannot be used hereafter for jewelry. Regimental jewelry, "V for Victory," and floral designs were popular, although geometric, Hindu, and Latin American motifs also were used. Ensembles set with similar stones were much worn. Clips and brooches were especially popular; bracelets (identification and charm bracelets

largely), earrings, and rings were also in demand.

Owing to the shortage of melee, pavé mountings are becoming rare. Topaz, amber, and aquamarine barbaric in size were used in bracelets and rings. Diamond (including some yellow stones), ruby, and sapphire (largely blue, but also yellow and pink) were the most popular gems, followed by topaz, aquamarine, amethyst, and amber. The insistent demand for diamonds and the patriotic motif in jewelry caused colorless stones to be dominant, followed by blue and red stones, then yellow and brown, and then green, purple, and black. The wide knowledge of gem stones, because of lectures by jewelers and courses in some colleges, is causing the American public to use a wider range of gem stones than ever before. Fine examples of certain of these stones are not too expensive, and some of them may be as beautiful as some of the noble gems.

#### DOMESTIC PRODUCTION

The production of gem stones in the United States in 1942 did not escape the blight of war, because producers sought minerals of greater strategic importance. Further, gas rationing in 1942 reduced not only collecting by amateurs but cut down the number of tourist customers who passed the lapidary's door. On the other hand, the shortage of foreign-cut stones improved the market for stones of American origin and cut. Intensified mining of pegmatitic ore bodies for block mica, beryl, and tantalite should have increased the production of aquamarine and other pegmatitic gem stones; but, if so, the miners appear to have high-graded the gem byproduct. Government-aided crystal mining (for radio plates) in Arkansas and California also probably increased the production of crystal suitable only for objets d'art. Makers of meerschaum pipes were short of the Turkish raw material, and satin spar was not available to the cutters of beads at Niagara

Falls. Restrictions on the use of silver in jewelry are said to have reduced the manufacture of turquoise-set jewelry by the Navajos.

It is believed that the net result of these various factors was a markedly smaller production of gem stones in 1942. A rough estimate of the value of uncut stones used in jewelry and related industries is \$150,000 with a total value after cutting of \$400,000; corresponding estimates in 1941 were, respectively, \$240,000 and \$770,000. Of the total value in 1942, sapphires (largely used industrially) represented 31 percent, turquoise 21 percent, and the quartz minerals 20 percent. The chief producing States in approximate order of output were Montana, Nevada, Oregon, and Wyoming.

Two corporations in Montana in 1942 produced sapphires weighing about 50,000 ounces (1.71 short tons) worth \$47,000; most of these stones were stock-piled for possible use as instrument jewels, although a few were cut for gems. American Gem Mines (Charles H. Carpp, manager) at Philipsburg was the principal producer; this company sold its product to the Government. The Perry-Schroeder Mining Co., a gold-dredging company operating near Helena, was permitted, after the orders closing gold mines were issued, to continue dredging because of its sapphire byproduct. The New Mine Sapphire Co. at Utica and the Simon property near Butte did not operate.

The Smith mine near Beowawe, Nev. (product sold in California), was the principal turquoise producer; it yielded 13,033 pounds valued at \$32,000. B. F. Couch reports that other Nevada turquoise miners produced about 350 pounds worth \$4,000. The King property, at Manassa, Colo., also produced considerable turquoise, and a small quantity is said to have been mined near Kingman, Ariz.

Cerrillos mine, near Santa Fe, N. Mex., was not operated.

Dr. H. C. Dake reports that in 1942 gem mining in the Pacific Northwest (Washington, Oregon, Idaho, Montana, and Wyoming) was only about half as active as in 1941, although cutting of agate cabochons increased. Part of the lapidary industry was converted to the cutting of radio quartz plates. Fine moss agate was discovered about 8 miles southeast of Willowdale, central Oregon; the agate is reported to occur as a thick vein in rhyolite, and about 4,000 pounds

worth \$4,000 is said to have been mined.

Fine moss agates continue to be recovered from the gravels of Yellowstone River in southeastern Montana, but in diminishing quantities. R. L. Harris, of Miles City, Mont., a jeweler and mossagate enthusiast, found on the banks of the Yellowstone a moss agate with a natural "V" for Victory on it. He had it cut and mounted in a ring of Montana silver and requested a national news weekly to present it to Winston Churchill; this was done, and the last leg of the journey was made in a ferry bomber. The Prime Minister was pleased to accept it. A little agatized wood, "rainbow" agate, and other forms of quartz are produced in Wyoming.

New occurrences of both green and black jade (nephrite) have been discovered in the general vicinity of Lander, Wyo. (personal communications of Fred Abernathy, Lloyd B. Curtis, H. C. Dake, and O. W. Plaga). Some of the green is of fine quality and worth \$5 a pound. Boulders of jade, one of which is said to weigh almost 2,000 pounds, occur in an area 20 miles long and 3 miles wide paralleling Sweetwater River. Black nephrite is reported to occur in place in granite, but the lighter green is known only as boulders. It is by no means impossible that after the war American jade will be exported to China.

A. M. Buranek reports that several hundred pounds of variscite were mined from the Clay Canyón deposit near Fairfield, Utah, and collectors obtained some variscite from Grantsville (Tooele County) and Lucin (Box Elder County). Fine agates and jaspers were obtained in eastern Utah. Considerable jet was collected from the Henry Mountains in southeastern Utah. Black obsidian with white christobalite inclusions, attractive when polished, has been found in Millard County, and some has been sold. Good topaz crystals were collected on Topaz Mountain, and pyrope garnet was obtained near

'Mexican Hat, San Juan County.

P. C. Leggett reports that several hundred carats of fine amethyst were produced in 1942 from two New Hampshire localities—Stark and Milan. The Stark locality, on Lone Mountain, is almost exhausted, but smoky quartz crystals occur rather abundantly in other "pockets" on the mountain. After heat treatment, the gem turns pale yellow. The Milan amethyst from Greens Ledge is not as fine as that from Stark, but the crystals are larger and less flawed. Gems of almost 30 carats have been obtained. Yellow, wine, blue, and colorless topazes also are found on Greens Ledge. Several good aquamarine crystals were found during the year in two mines in North Groton. Deeply colored, asteriated rose quartz was produced near the French mine in Gilsum.

Hugh D. Miser (see Bibliography) considers the veins from which the Hot Springs (Ark.) quartz crystals are obtained to be hydrothermal deposits of probable magmatic origin of mid-Pennsylvanian age. Although some of the finer crystals are sold for jewelry under the trade name "Hot Springs diamonds," most are sold to collectors or to constructors of water fountains and religious and memorial shrines. He estimates the value of crystals sold in 1941 at \$12,000. Some are cut into radio oscillators. Crystals weigh from a small fraction of an ounce to 330 pounds. Certain localities furnish beautiful crystals of

smoky quartz.

Other gems produced in the United States in 1942 included alabaster (South Dakota); albite (Maine); amazonstone (near Bar Harbor, Maine); amethyst (Maine); aquamarine (Amelia, Va.; Avon, Idaho); asteriated quartz (Wyoming); caesium beryl (Maine); lepidolite (Maine); moss agate (Siskiyou and San Bernardino Counties, Calif.); pipestone (Minnesota); rock crystal (Arkansas); rose quartz (Maine and South Dakota); greenish spodumene (Maine); topaz (Maine); tourmaline (Maine); and californite, a variety of vesuvianite, (Siskiyou County, Calif.).

## CANADA GEM STONES

Dr. A. L. Parsons reports that a little rock crystal was discovered in 1942 in Leeds County, Ontario; otherwise, the industry, never

important, was dead.

The Royal Ontario Museum at Toronto has a fine collection of Canadian gem and decorative stones, notably agate (Bay of Fundy and Thunder Bay district, Ontario); amethyst (Nova Scotia and Thunder Bay district, Ontario); and rose quartz (Lyndock Township, Ontario, and Manitoba). The rose quartz is deep in color and has

been used commercially to some extent. Included, also, are peristerite, an iridescent feldspar (Monteagle Township, Ontario); sodalite (Bancroft, Ontario, and Ice River, British Columbia); aquamarine (rare, Lyndock Township, Ontario, and southeastern Manitoba); golden beryl (rare, Manitoba); yellow scapolite (Grenville Township, Quebec); and amber (Cedar Lake, Manitoba).

#### IMPORTS 1

Imports of precious and semiprecious (real and imitation) stones (exclusive of industrial diamonds) totaled \$28,449,422 in 1942, a 16-percent decrease from 1941. Details are as follows:

Precious and semiprecious stones (exclusive of industrial diamonds) imported for consumption in the United States, 1941-42

네트 및 생활을 받으면 일반하는데		1941	1942		
Commodity	Carats	Value	Carats	Value	
Diamonds:					
Rough or uncut (suitable for cutting into gem stones),	Taran and				
duty-free	215, 026	\$10, 301, 371	277, 826	\$11, 518, 085	
Cut but unset, suitable for jewelry, dutiable	229, 582	18, 346, 415	125, 806	14, 599, 770	
Emeralds:	1				
Rough or uncut, free			6, 506	676	
Cut but not set, dutiable	22, 160	313, 185	21, 209	205, 717	
Pearls and parts, not strung or set, dutiable:		007 070		170 100	
Natural		387, 053		179, 169	
Cultured or cultivated	-	469, 676			
Other precious and semiprecious stones: Rough or uncut, free		107, 610		72, 387	
Cut but not set, dutiable		2, 968, 129		1, 580, 705	
Imitation, except opaque, dutiable:		2, 500, 125		1,000,100	
Not cut or faceted		10,962		195	
Cut or faceted:		10,002			
Synthetic		244, 264		86, 829	
Other		534, 070		97, 573	
Imitation, opaque, including imitation pearls, dutiable		33, 377		2, 622	
Marcasites, dutiable:	1			l	
Real		28, 228		104, 150	
Imitation	-	7, 136		1, 544	
		33, 777, 215		28, 449, 422	
		00, 111, 210		20, 110, 124	

## METAL SHORTAGES IN AMERICAN JEWELRY TRADE

Most of the common metals normally utilized in costume jewelry were diverted to national defense in 1941; and in 1942 use of most of the other metals in jewelry was prohibited. Limited amounts of domestic silver are still available, as, of course, is gold. Small amounts of the copper necessary to harden these metals can be used until June 30, 1943. The use of platinum, iridium, and rhodium in jewelry is forbidden. However, palladium alloyed with ruthenium is an acceptable substitute for platinum. Incidentally, should the need for it arise, the diamond-set platinum jewelry of United States citizens constitutes a considerable reserve of two critical materials for war purposes—platinum and diamonds. The Canadian manufacturer of jewelry is restricted even further, because the use of palladium is forbidden.

PRICE CEILINGS

Jewelry prices were frozen in June 1942 to the level effective during March 1942, although this did not affect "precious stones" as defined

<sup>&</sup>lt;sup>1</sup> Figures on imports compiled by M. B. Price, of the Bureau of Mines, from records of the Departments, Commerce.

by the Office of Price Administration. A precious stone, according to the OPA, is "any ruby, sapphire, emerald, natural pearl or any diamond weighing more than 1 carat or any semiprecious stone, after sale by the cutter, when the cutter has received more than \$100 for sale of the stone." In addition, when "two or more diamonds with an aggregate weight of 1.5 carats are set in one mounting," the diamonds shall be deemed precious. According to this definition a faded ruby, a watery sapphire, or a badly flawed emerald weighing a carat is precious, but a half-carat, flawless, well-cut diamond is not.

## CONVERSION OF THE JEWELRY INDUSTRY

The jewelry industry—as it produces in part articles of no value to the war effort and as it has been shorn of many of its raw materials—has been converted to war work to the greatest possible extent. Some of the larger units are wholly converted, the smaller less completely so, although some of the smaller shops, by pooling, have obtained valuable subcontracts. Silverware plants are making munitions; a firm formerly manufacturing expensive jewelry is now cutting quartz plates for radio work; and watch factories are turning out instrument jewels.

#### GOVERNMENT REGULATIONS

Every government, from the smallest to the largest, since the war began has had to formulate a host of regulations for the jewelry trade. The principal objects were to divert funds normally spent on jewelry to government securities, to discourage exportation of easily converted wealth, and to prevent critical material and needed skilled labor from being used to produce unessential merchandise.

## EFFECT OF WAR ON THE GEM-STONE TRADE

In 1942, the United Nations lost Burma and thereby an important source of ruby, sapphire, spinel, jade, and tourmaline. On the other hand, when Dakar sided with the Fighting French, the Axis Powers lost the most important source of industrial diamonds remaining to them.

There is no shortage of gem diamond, ruby, emerald, and sapphire in America, nor of most of the less expensive precious stones, with the possible exception of zircon. The "good-neighbor policy" is making Americans more familiar with the lovely tournaline, aquamarine, and topaz of South America. The lapidaries of the Northwestern States are cutting many agate and jasper cabochons for mountings of inexpensive jewelry. Supplies of synthetic stones and imitations are inadequate.

Owing to the war, Indian and Ceylonese stones (especially sapphire and star sapphire) arrive in New York direct instead of via Paris and London, as formerly. By air mail, elapsed time is 3 or 4 weeks.

Nazi puppets in the Netherlands, Croatia, and other dependencies continue to rob Jews of their jewelry, in instances having the effrontery to pretend that the funds which the jewels represent will be administered in favor of the victims.

Americans in India are buying jewels for souvenirs on an extensive scale. Jaipur, the principal Indian cutting center, has never been busier. As the business ethics of the average Hindu jeweler are low,

The state of the s

some American soldiers will find themselves possessing fine bits of glass; others will acquire jewels that will serve as heirlooms for generations to come. Algerian goldsmiths look upon the arrival of Americans as a reasonable excuse to quadruple prices.

#### DIAMOND

The diamond industry had its most prosperous year in over a decade, owing to unprecedented sales of industrial diamonds. Rough, suitable for gem cutting, also was sold in considerable quantity.

Production continued in 1942 at about the 1941 rate, although it was only 69 percent of that in 1940. A large part of the product of the mines of central and northwest central Africa—only African mines now operating—is of industrial grades, but the gem stones recovered are sufficiently valuable to keep industrial prices reasonable. Prices of rough and fine large cut continued to advance; those of small cut declined somewhat. In fear of inflation, "investment" buying increased in the black markets of Europe and the free market here.

Share dealings.—The shares of diamond-mining companies, virtually all of which are listed on the London Stock Exchange, gained over one-third in value in 1942. Their record was much better than that of the British industrials or American stocks in general. Frequently

they were market leaders.

Stocks were hesitant for the first quarter, then advanced sharply; fell, owing to the British set-back in Libya, but from mid-July to the year end gained markedly. At the close of the year stocks stood at 560 percent of the all-time low (1932) and at 52 percent of the all-time high (1927). Nearly all the companies paid dividends in 1942, several

at increased rates.

Market.—In 1942, the Diamond Trading Co., which in normal times controls the sale of about 95 percent of the world output, sold rough to the value of well over £10,500,000. "American qualities" (large fine rough) and fine small goods enjoyed a satisfactory market, but probably over 40 percent of the sales were of industrials. In mid 1942 the British Government appointed C. H. Rodwell diamond controller. The Trading Co. branch office at Hamilton, Bermuda, is said to have been closed recently, all stocks on hand having been sold.

In 1942 America bought large quantities of medium-size cut, particularly in the second half of the year. The other warring nations bought what they could, usually in "black" markets at fantastic prices. In time of war diamonds are natural "investments" to the enslaved people of a conquered country and to citizens of a belligerent country

whose war future is dismal.

Prices of rough diamonds early in the year advanced 5 to 20 percent, according to qualities. Fine cut advanced 10 to 15 percent; melee slumped 30 percent in the first half of the year but rallied and was off but 10 percent at the year end.

Stocks of rough decreased markedly in 1942, as consumption exceeded production. Stocks in the hands of American cutters are probably adequate, as are those of fine large cut; the supply of small

cut is abnormally low.

Imports.—As the following table shows, 1942 imports of gem diamonds were 91 percent of those of 1941, a small gain in rough imported being offset by a larger loss in cut. The quality of cut imported was excellent; that of rough was mediocre.

# Diamonds imported into the United States, 1941-42, by countries [Exclusive of industrial diamonds]

	R	lough or unc	1t	Cut but unset			
Country	Carats			Carats	Value		
	Carats	Total	Average	Carais	Total	Average	
1941	1						
Argentina				146	\$8,607	\$58.95	
Belgium Brazil British Malaya				145, 504	8, 298, 551	57.03	
Brazil	63, 710	\$2, 280, 628	\$35.80	7, 434	678, 099	91. 22	
British Molovo	00, 110	Ψ2, 200, 020	000.00	286	19, 878	69, 50	
Cuba				205	17, 808	86.87	
France				4, 950	726, 665	146.80	
Germany				539	42, 337	78, 55	
Uong Vong				9	596	66. 22	
Hong Kong				443	35, 930	81. 11	
Mexico					76, 565	50.34	
Netherlands				1, 521	5, 339	51. 34	
Netherlands Indies				104			
Palestine				5, 523	703, 293	127.34	
Switzerland Union of South Africa				630	108, 796	172.69	
Union of South Africa	150, 324	7, 986, 039	53.13	42, 326	5, 450, 923	128.78	
U. D. D. IL.				30	2, 250	75.00	
United Kingdom				19, 932	2, 170, 778	108. 91	
Venezuela	992	34, 704	34. 98				
	215, 026	40, 301, 371	47. 91	229, 582	18, 346, 415	79. 91	
1942							
Argentina				36	32, 013	889.25	
Belgian Congo	205	4, 573	22, 31				
Belgium and Luxembourg		1,0.0		26, 755	2, 042, 757	76.35	
Brezil	6 320	477, 812	75, 60	23, 842	2, 686, 071	112.66	
British Aniona	501	10 775	33 46	55	5, 810	105.64	
Brazil British Guiana British Malaya	001	10, 110	00. 10	278	19, 628	70.60	
Conedo				2.0	395	395.00	
Canada Colombia				18	2,666	148.11	
Cube				2,746	321, 863	117. 21	
CubaFrance				1, 327	184, 250	138, 85	
Common				1, 327		46, 42	
Germany				102	7,520	40. 42	
India and Dependencies (British India)				1	50	50.00	
Mexico				365	41, 211	112. 91	
Netherlands				960	83, 341	86.81	
Notherlands Indies				117	13, 579	116.06	
Netherlands Indies Palestine and Trans-Jordan (Pales-				111	10,019	110.00	
tine)				90 500	2, 989, 910	145, 84	
Switzerland				20, 502		110. 55	
DWILZERIALIQ	050 500	10 504 405	41 07	175	19,346		
Union of South Africa	202, 080	10, 524, 425	41.67	35, 153	4, 738, 062	134. 78	
	1, 683	102, 154	60.70	13, 307	1, 410, 598	106.00	
	2, 000						
United Kingdom <sup>1</sup> Venezuela	16, 447	389, 346	23, 67	6	700	116. 67	

<sup>&</sup>lt;sup>1</sup> United Kingdom of Great Britain and Northern Ireland.

Cutting.—In 1942 diamond cutting ceased its recent rapid growth, due partly to a slightly smaller demand for large cut but mostly to

the diversion of artisans from gem to industrial cutting.

Now that the Low Countries are no longer factors in the cutting industry, the United States (750 cutters and 750 apprentices) and Palestine (reported as 2,500 cutters) are the largest cutting centers, followed by South Africa (400 cutters), Great Britain (300), Puerto Rico (75), and Cuba (66). Java, Borneo, and Brazil cut some diamonds for their local trade, but the cutting is not done well enough to satisfy the American trade.

Several of the belligerents propose to train their wounded as cutters, notwithstanding the unfortunate outcome of similar experi-

ments after the First World War.

World production.—For the third year, due to the war, accurate diamond-production statistics are not available, but the estimates in

A Company of the second

the following table are believed to be fairly accurate. World production (gems and industrials) in 1942 is estimated to have been 9,254,200 carats (1.851 metric tons) valued at \$28,000,000. Compared with 1941, the weight increased somewhat more than 1 percent, and the value did not change. The quality was similar to that of 1941, bort representing about 79 percent of the total and gem stones Belgian Congo was the leading producing country, both 21 percent. in weight (65 percent of the total) and in value (29 percent). British Empire produced 22 percent of the total by weight and 33 percent by value. As the South African pipe mines were not operated, all production was from alluvial mines.

The following table shows, as accurately as available statistics

permit, world production for the past 5 years.

World production of diamonds, 1938-42, by countries, in metric carats [Including industrial diamonds]

Country	1938	1939	1940	1941	1942
Africa:		: "			
Angola	651, 265	690, 353	784, 270	787, 000	1 791, 850
Belgian Congo	7, 205, 620	8, 360, 000	9, 603, 000	5, 866, 000	6, 018, 000
French Equatorial Africa	16,013	1 16, 000	1 16,000	20,000	20,000
French West Africa	61,928	56, 314	1 75, 000	35, 000	36,000
Gold Coast 2		1, 087, 652	1 825, 000	1,000,000	1,000,000
Sierra Leone	689, 621	1 600,000	750,000	850, 000	1 850, 000
South-West Africa	154, 856	35, 470	30/017	46, 578	60,000
Tanganyika (exports)	3, 576	3, 445	2, 250	1 1, 750	1,000
Union of South Africa:					
Mines	979, 460	1, 089, 144	1 371, 447		
Alluvial	259, 147	160, 684	1 172, 027	112, 300	<sup>3</sup> 106, 000
Total Union of South Africa	1, 238, 607	1, 249, 828	1 543, 474	112, 300	* 106, 000
Brazil	235, 000	1 350, 000	1 325, 000	325,000	300, 000
British Guiana	32, 522	32, 491	1 26, 764	27,000	27,000
Other countries 4	34, 200	19,000	31, 750	34, 350	44, 350
Grand total	11, 619, 971	12, 500, 553	13, 012, 525	9, 104, 978	9, 254, 200

<sup>1</sup> Estimated

† Estimated.

2 1938-40: Exports; 1941-42: Production.

3 South African production without Namaqualand was about 76,505 carats.

4 1938: U. S. S. R., India, Borneo, New South Wales, and Venezuela; 1939: Venezuela, India, Borneo, New South Wales, and U. S. S. R., and Venezuela (Venezuela produced 29,399 carats); 1942: Borneo, India, New South Wales, U. S. S. R., and Venezuela (Venezuela produced 29,399 carats); 1942: Borneo, India, New South Wales, Rhodesia, U. S. S. R., and Venezuela (Venezuela produced 34,084 carats).

Both Angola and Belgian Congo showed slightly greater production; but the decrease in South Africa was rather marked, indicating near exhaustion of its alluvial diggings.

In 1942 some of the companies attempted to increase production of the industrial stones so necessary today and succeeded in a small If the war continues, however, the long-term outlook is for a drying up of production, as certain essential supplies will be lacking owing to the isolation of the mines now producing.

Industrial diamonds.—In these days industrial diamonds steal the limelight from the gem variety, not only as to sales but as to romance. Concerning the latter, we may cite the recovery of several shipments snatched by the Allies from under the eyes of the Axis Powers.

The use of industrial diamonds, particularly of crushing bort, continues to increase beyond the expectations of anyone in the industry. Part of this expansion, of course, is due to the war program; but after the war is over, industrial diamonds will retain much of their gain in use. Consumption greatly exceeds production.

finer grades continue to be scarce, but users are schooling themselves

to utilize advantageously the grades that are available.

Germany and Italy are already feeling a shortage of industrial diamonds. Germany's shortage is dramatically indicated by the fantastic prices charged in the Swiss "black" market. Japan is in an even less enviable position, as it has not a store of gem stones to which it can resort.

Wholesale prices of industrials in 1942 remained firm; retail prices strengthened. During the year the War Production Board tightened

its regulations as to transactions in industrial diamonds.

In pre-war days the percentages, by value, of the chief uses for industrial diamonds were as follows:

Diamond drilling_				Percent
Diamond-set tools. Diamond dies			 	30–35 10– 7
Crushing bort (bor Miscellaneous	ided wheels and	tools)	 	 10- 7
wrightenes			 	 5–11

Today the use of crushing bort is much greater, and the use of diamond-set tools and of dies is relatively greater, largely at the expense of diamond consumption in drilling.

Imports of industrial diamonds into the United States during

the past 5 years were as follows:

Industrial diamonds (glaziers', engravers', and miners') imported into the United States, 1938-42

Year	Carats	value Year			Val	ne	
	Caracs	Total	Average	Year	Carats	Total	Average
1938 1939 1940	1, 396, 247 3, 568, 730 3, 809, 071	\$4, 213, 412 9, 725, 683 11, 026, 563	\$3. 02 2. 73 2. 89	1941 1942	6, 882, 248 11, 203, 704	\$14, 908, 809 22, 154, 076	\$2. 17 1. 98

## RUBY, SAPPHIRE, EMERALD

In Indian Precious Stones, by L. A. N. Iyer (Bull. 6, Records of the Geological Survey of India, Calcutta, New Delhi, 1942, pp. 17–23), the Indian sapphire localities of Afghanistan, Burma, and Ceylon are described. In its 40-year life (1885–1925), the average annual gross of the Burma Ruby Mines Co. was only about \$300,000, sufficient reason why the company expired some years ago. The local natives carry on mining in a crude way, either by shallow shafts from which the "byon" is removed and robbed laterally as far as safety permits; by terracing the sides of a hill, somewhat after the Colombian mining practice; or by collecting gravels from limestone caves. The gravels are treated in an open, slightly sloping pond, in which the valuable gems sink and the valueless sands are washed away.

Edward Gübelin (see Bibliography) described the rather distinctly differing microscopic and other characteristics of sapphires from the

major fields (Kashmir, Burma, Thailand, and Ceylon).

Company of the second

#### LESSER GEMS

Jade (nephrite) occurs in Burma in place in a dike, in a Tertiary conglomerate derived from it, and in modern stream gravels (Indian Precious Stones, by L. A. N. Iyer, pp. 38-41). Mining is confined to the dry months, March to May. Although the finer cutting is done in China (75 percent of the product is exported to that country), some stones are cut in Mandalay. The market depends on the prosperity of China; hence, at present it is depressed.

In 1940, Madagascar produced 4,400 pounds of agate, 1,004 pounds of rock crystal, and 28,508 troy ounces of precious stones of various classes. Its beryl, amethyst, and particularly its amber are fine.

Brazil is rich in precious stones. Its diamond and quartz crystal are mentioned elsewhere; one report states that in the first 9 months of 1941 Brazil exported the following additional gem stones to the United States:

	Kind		Quantity	Value, milreis
Aquamarine		 _grams	26, 080	1, 912, 092
Amethyst		 do	45, 286	666, 336
Tourmaline		 do	3, 412	238, 027
Topaz		 do	16, 561	175, 821
Agate		 kilos	5, 410	83, 076
Other gem stones		 _grams	371, 129	1, 431, 107

About 63 percent of these exports reached the United States. Total exports of aquamarine in 1940 were reported to have been 1,169,034 grams, worth about \$667,000, and in 1941, 524,651 grams, worth about \$550,000. Brazil's cutting industry employs about 2,500 artisans.

An aquamarine weighing 109 kilos was found early in the summer of 1942 at Ariranho in the State of Minas Gerais. The owners were at once offered 800 contos for the stone, or about \$40,000. A short time before, a fine block of rock crystal weighing 480 kilos had been

found in the same region.

South-West Africa formerly sold its precious stones to the Germans; in consequence, since the war began very little if any mining has been done. In 1939, however, 4,075,031 grams of precious stones were produced, and 9,226,269 grams, worth £1,132, were exported to Germany. The principal stones were aquamarine, heliodor (golden yellow beryl), tourmaline (blue, through green, to a pale yellow-green), rose quartz, and chalcedony. A few colorless or light-blue topazes are also produced around Leideritz Bay in the diamondiferous gravels, and some agate. Apparently, so far as aquamarine, tourmaline, and topaz are concerned, the pegmatite druses at the surface are more or less exhausted. The unweathered rock is hard, requiring the use of dynamite in mining, and any gem stones recovered from such rock are likely to be flawed.

#### INSTRUMENT AND CHRONOMETER JEWELS

Before the war, the United States imported virtually all its instrument and watch jewels from Europe, particularly from Switzerland. Without such jewel bearings, high-grade instruments and chronometers to guide our aviators and to assist our bombardiers and Navy officers cannot be made. When war came, plants were created in this country to produce synthetic sapphire, and stocks of Montana sapphire were set aside as a reserve. Simultaneously, mechanical means of

fabrication were introduced. The program is apparently approaching successful completion. In addition, certain hard-glass bearings are being made, which will alleviate the situation. Imports for consumption of jewels for any movement, mechanism, device, or instrument or for any meter or compass numbered 92,547,236, valued at \$2,007,012, in 1941 and 36,649,359, valued at \$1,015,788, in 1942. 1942 the use of instrument jewels was confined to essential war work (WPB. M-50, amended Nov. 2, effective Nov. 2, 1942).

#### BIBLIOGRAPHY

- Anderson, B. W. Gem Testing for Jewelers. Heywood & Co., London, 1942, 194 pp. \_ \$2.
- BALL, SYDNEY H. The Diamond Industry in 1942. Jewelers' Circular-Keystone,
- New York, July 1943, 16 pp.

  Baxter, Wm. T. Jewelry Gem Cutting and Metalcraft. McGraw-Hill, New York, 2d ed., 287 pp., 1942. \$2.75.

  CHESLEY, FRANK G. Investigation of the Minor Elements in the Diamond. Am. Mineral., vol. 27, January 1942, pp. 20-36.

  GÜBELIN, EDWARD. Local Peculiarities of Sapphires. Gems and Gemology, Los Angeles, Calif., Fall 1942, pp. 34-39; Winter 1942-3, pp. 50-54.

  IYER, L. A. N. (Precious Stones). Bull. 6, Economic Minerals. Geol. Survey of India Dalbi 1942, 1e 6d.

- of India, Delhi, 1942. Is 6d.

  Kerr, Paul F., and Armstrong, Elizabeth. Recorded Experiments in the Production of Quartz. Bull. Geol. Soc. America, vol. 54, suppl. I, April
- 1943, pp. 1-34. LARSEN, ESPER S., 3d. The Mineralogy and Paragenesis of the Variscite Nodules from Near Fairfield, Utah. Am. Mineral., vol. 27, 1942, pp. 281-300, 350-372, 441–451.
- MISER, HUGH D. Quartz Veins in the Ouachita Mountains of Arkansas and Oklahoma. Econ. Geol., vol. 38, March-April 1943, pp. 91-118.

  NORTHROP, STUART A. Minerals of New Mexico. Bull. Univ. of New Mexico, Albuquerque, N. Mex., 387 pp. \$1.

  NOTT, STANLEY CHARLES. Chinese Jades in the Stanley Charles Nott Collection.

- Palm Beach, Fla., 536 pp. \$50.

  Roebers, Austin F., and Sperisen, Francis J. American Synthetic Emerald.

  Am. Mineral., vol. 27, 1942, pp. 762–768.

  Ross, Clarence S. Origin and Geometric Form of Chalcedony-Filled Spherus
- lites from Oregon (Thundereggs). Am. Mineral., vol. 26, 1941, pp. 727-732. Symons, Henry H. Quartz Gems of California. Rocks and Minerals, vol. 15,
- February 1940, pp. 38-44.
  Young, Fred S. The Art of Gem Cutting Complete. The Mineralogist Publishing Co., Portland, Oreg., 2d ed. 112 pp.

## NITROGEN COMPOUNDS 1

By BERTRAND L. JOHNSON

#### SUMMARY OUTLINE

	Page		Page
General conditions	1521	Inorganic nitrogen compounds—Continued.	- 450
Inorganic nitrogen compounds	1522	Synthetic nitrogen compounds	1523
Natural nitrates	1522		1523
Domestic nitrate deposits	1522		1523
Chilean nitrates	1522		1524
		Cyanamid	1524
		Organic nitrogen compounds	1524

#### GENERAL CONDITIONS

Nitrogen, in various compounds, is an essential element in the domestic economy of the United States. About 500,000 short tons were consumed in this country yearly in normal pre-war times nearly 400,000 tons in agriculture and the remainder in industry. The current war increased the domestic need for nitrogen for both agricultural and industrial purposes far beyond productive capacity or importation possibilities available at its start. The result was a shortage in nitrogen. In the recent past the demand for this element was met largely from domestic sources, but an important part of the supply has necessarily come from foreign countries, as the United States in the past was never self-sufficient in nitrogen supply.<sup>2</sup>

The war cut off some imports, hindered the importation of other commodities, and seriously disturbed the domestic nitrogen economy. Munitions factories had first call on the lessened nitrogen supply, and the military demands for nitrogen were so great that there was not enough for agricultural needs. Restrictions were placed on the use of nitrogen in fertilizers, and one after another of the nitrogen compounds was placed under allocation. Consumption in 1942 was exceedingly heavy, and the supply did not equal the demand either for munitions or agricultural use. Agriculture attempted to turn to organic nitrogenous materials for fertilizer use, and new synthetic nitrogen plants were started to satisfy the demand for explosives. On January 1, 1943, there had been built or were in process of construction in the United States synthetic and byproduct nitrogen plants with the huge capacity of at least 1,725,000 tons of nitrogen, a quantity nearly three times as great as the maximum pre-war consumption of nitrogen for all purposes. Development of this great productive capacity will release the United States from dependence upon foreign countries for supplies of this vital material, but it will introduce a hazard in the post-war economy because it exceeds any peacetime requirements that can now be foreseen.

A CONTRACTOR OF THE CONTRACTOR

<sup>1</sup> Latest previous chapter on this subject: Mansfield, G. R., Nitrates: Geol. Survey Mineral Resources, 1922, part II, 1923, pp. 39-40.
2 Johnson, Bertrand L., Nonmetallic Minerals Needed for National Defense. 1. Fertilizer Materials: Bureau of Mines Inf. Circ. 7159, 1941, 6 pp.

#### INORGANIC NITROGEN COMPOUNDS

#### NATURAL NITRATES

Domestic nitrate deposits.—Deposits of soluble nitrate minerals are widely distributed in small quantities in the United States. Nitrate deposits have been found in 23 States, including the humid States Pennsylvania, Tennessee, and Alabama, but occurrences are much more numerous in the arid and semiarid parts of the West. Three types of nitrate deposits are known—cave, caliche, and playa. cave nitrates are most widely distributed; the caliche and playa types occur only in the arid regions. The cave deposits contain the widest variety of nitrate salts, including potassium, sodium, calcium, and (more rarely) magnesium and ammonium nitrate. The caliche and playa deposits are chiefly sodium nitrate. The deposits are discussed in detail in various Geological Survey reports.3

The known natural nitrate deposits in the United States are too small and too low-grade to serve as a basis for a domestic nitrate industry. Furthermore, the general conditions under which nitrates occur in nature are quite well known, and this knowledge affords little hope that deposits of commercial size or quality will ever be found.

The United States has no domestic production of natural nitrates, so far as known. Cave nitrates were used occasionally in the past. The domestic caliche and playa nitrate deposits have never been worked.

Chilean nitrates.—Natural sodium nitrate and smaller quantities of potassium-sodium nitrate are imported from Chile. All Chilean nitrate of soda imported from July 1, 1942, to the end of the year was for the account of the Defense Supplies Corporation, a subsidiary of the Reconstruction Finance Corporation.

Sodium nitrate imported into the United States, 1938-42

	(	Chile	Total				Chile	r	'otal
Year	Short tons	Value	Short tons	Value	Year	Short tons	Value	Short tons	Value
1938 1939 1940	644, 942 676, 409 744, 145	\$10, 689, 289 11, 199, 895 12, 451, 179	646, 386 676, 917 744, 145	\$10, 731, 678 11, 213, 445 12, 451, 179	1941 1942	610, 561 899, 785	\$10, 868, 222 17, 213, 549	610, 569 899, 845	\$10, 868, 568 17, 216, 194

Potassium-sodium nitrate (all from Chile) imported into United States, 1938-42

Year	Short tons	Value	Year	Short tons	Value
1938	44, 493 55, 164 55, 016	\$971, 646 1, 235, 078 1, 366, 131	1941 1942	34, 541 14, 272	\$725, 846 377, 703

Imported and synthetically produced domestic sodium nitrates are under allocation—approximately 80 percent for agricultural and the

<sup>&</sup>lt;sup>8</sup> Mansfield, G. R., and Boardman, Leona, Nitrate Deposits of the United States: Geol. Survey Bull.

National G. R., and Boardman, Leona, Nitrate Deposits of the Officer States. Geof. Survey Bull. 838, 1932, 107 pp.
Noble, L. F., Mansfield, G. R., and others, Nitrate Deposits in the Amargosa Region, Southeastern California: Geof. Survey Bull. 724, 1922, 99 pp.
Noble, L. F., Nitrate Deposits in Southeastern California, with Notes on Deposits in Southeastern Arizona and Southwestern New Mexico: Geof. Survey Bull. 820, 1931, 108 pp.
Gale, H. S., Nitrate Deposits: Geof. Survey Bull. 523, 1912, 36 pp.

at the second se

The second second

remaining 20 percent for industrial uses. Control of allocation is under General Preference Order M-62 of January 15, 1942, effective February 1, 1942.

A stock pile of Chilean nitrate was started in Chile in 1941 by the

United States Government.

#### SYNTHETIC NITROGEN COMPOUNDS

General.—The general situation with respect to chemical nitrogen up to the entrance of the United States into World War II is wellcovered by recent publications.4

The following summary presents the major developments in the

leading chemical nitrogen products in 1942.

Ammonia and its compounds.—In the United States ammonia (NH<sub>3</sub>) is made principally by the high-temperature reaction of pure nitrogen and hydrogen under pressure in the presence of a catalyst. A relatively smaller quantity is recovered as a byproduct of the coking of coal. Ammonia is now used principally in military explosives, and, to a slightly smaller extent, in the manufacture of nitrogenous fertilizers. Smaller quantities are used in industrial explosives, chemicals, and in various minor ways. Agricultural consumption in 1941 has been estimated at about 65,200 short tons of nitrogen in the form of anhydrous ammonia and ammonia liquors; consumption in 1942 is believed to have decreased because during part of the year the use of these commodities for the direct ammoniation of superphosphate was prohibited.

Although the production of synthetic ammonia at privately owned and Government plants made an all-time record in 1942, the supply was still short because of the greatly increased demand for its use in

making munitions and in other war industries.

The United States capacity for the production of synthetic ammonia is being vastly increased. Several new plants have been erected, and others are in process of erection. It is reported that eventually there will be synthetic-ammonia plants in 10 or more States.

General Preference Orders M-163 and M-164, effective June 1, 1942, placed both byproduct ammonia and synthetic ammonia under complete allocation by the War Production Board. There was no

Government stock piling in 1942.

Ammonium sulfate is one of the most important agricultural fertilizers and one of the principal sources of nitrogen in mixed fertilizers. Production increased in 1942 over 1941, but sales declined from 756,569 short tons in 1941 to 751,914 tons in 1942. In 1941, agricultural consumption of this commodity in the United States totaled 138,248 short tons of contained nitrogen, or 30.6 percent of the total nitrogen consumed in agriculture.5

Byproduct ammonium sulfate was placed under allocation by the War Production Board in General Preference Order M-163 of May 30, 1942, effective June 1, 1942. Allocation did not change the use pattern, and most of the ammonium sulfate is stated by the War

<sup>4</sup> U. S. Tariff Commission, Chemical Nitrogen: Rept. 114, 2d ser., 1937, 300 pp.
Johnson, Bertrand L., Work cited in footnote 2.
Schallis, A. H., Nonmetallic Minerals Needed for National Defense. 3. Nitrates: Bureau of Mines Inf.
Circ. 7170, 1941, 6 pp.
Mehring, A. L., Consumption of Commercial Nitrogen as Fertilizer in 1941: Fertilizer Review, vol. 17,
No. 3, 1942, pp. 2-3, 11-13.

Production Board to have gone to the fertilizer industry, but smaller

quantities were allocated than before.

Ammonium nitrate, hitherto used chiefly in the manufacture of explosives, is being utilized to a considerable extent as a nitrogenous fertilizer. Tennessee Valley Authority Nitrate Plant No. 2 at Muscle Shoals, Ala., was modernized and rehabilitated in 1942 and began to produce and ship ammonia nitrate for explosives and later for fertilizers. Imports of a mixture of ammonium nitrate and limestone, produced in Ontario, Canada, were released by the War Production

Board early in 1943 for direct application to the soil.

Sodium nitrate.—When the United States entered World War II, only one domestic establishment was producing synthetic sodium nitrate—the Hopewell (Va.) plant of the Allied Chemical & Dye Corporation. Several new domestic plants were erected and began operations in 1942. The production capacity of synthetic sodium nitrate plants in the United States at the end of 1942 has been estimated at about a million tons annually, but this capacity could be attained only at the expense of reducing supplies of ammonia available for other purposes. Most of the domestic synthetic nitrate of soda produced in 1942 is reported to have gone to munitions plants, and the remainder to fertilizer consumers. The allocation of synthetic nitrate of soda is covered by the same order (General Preference Order M-62) as is Chilean nitrate.

Cyanamid.—Imported Canadian calcium cyanamid, a synthetic fertilizer, has contributed materially to meeting United States needs. It has been produced since about 1910 at the plant of the American Cyanamid Co., of New York, at Niagara Falls, Canada. Domestic production has been limited to a single venture of the United States Government. Nitrate Plant No. 2 at Muscle Shoals, Ala., was originally erected as a cyanamid plant, but except for a 2-week trial run in 1919 it was never operated. Calcium cyanamid is, like other chemical nitrogen fertilizers, under allocation (Conservation Order

M-231).

## ORGANIC NITROGEN COMPOUNDS

Organic nitrogenous materials of vegetable or animal origin, such as tankage, fish scrap, cottonseed meal, castor pomace, dried blood, guano, bones, sewage sludge, and tobacco stems, are utilized entirely in the fertilizer and feed industries and compete with chemical nitrogen products. The best grades, however, contain an average of only 5 to 12 percent nitrogen. The demand for some of these materials for animal feed is increasing.

Restriction in the use of chemical nitrogen in fertilizers after September 1942 resulted in an increased demand for organic nitrogen compounds, and competitive bidding by feed makers and fertilizer

interests led to shortages and unequal distribution.

## MINOR NONMETALS

By G. RICHARDS GWINN 1

#### SUMMARY OUTLINE

	Page	👔 nagara katan basa da kacamatan 🖟 💮	Page
Carbon dioxide	1525	Monazite	1533
Graphite	1525	Olivine	1534
Kyanite, and alusite, and dumortierite	1528	Quartz crystal	1535
Lithium minerals	1530	Strontium minerals	1536
Mineral earth pigments and manufactured		Topaz	1536
iron oxide pigments	1531	Vermiculite	1536

#### CARBON DIOXIDE

Carbon dioxide, widely known as a means of supplying sparkle and palatability to carbonated beverages and in its solid form as a highly efficient refrigerant, has constantly increasing utility in war equipment. In this field it is used as a fire extinguisher in tanks, trucks, and air-

planes and as an inflating agent for life preservers and rafts.

Production of commercial carbon dioxide in the last 6 months of 1942, as compiled by the Chemical Branch of the War Production Board, was 146,173 short tons of dry ice valued at \$7,308,650 and 76,981 short tons of liquid and gas. The value of carbon dioxide in liquid or gaseous form ranges from 1 cent to 8 cents per pound, depending on the purity of the product; as the total for liquid and gas is given as one, no attempt has been made by the Bureau of Mines to compute an average or total value.

#### GRAPHITE

Demand for all qualities of graphite, except natural amorphous, was greater in 1942 than in 1941; demand for crucible-grade material was greatest. Aided by conservation orders and restrictions, stocks of both Madagascar flake and Ceylon lump were at higher levels than in 1941.

Graphite has been placed on the critical materials list, but only about 10 percent of the graphite employed in the United States has critical importance. This is principally flake graphite from Madagascar, used in crucibles. Although the advent of electric furnaces for manufacturing high-grade steel reduced the demand for graphite crucibles, fairly large numbers are still used in melting nonferrous metals and some steels. Flake graphite is used also in retorts for smelting and refining zinc and brass.

On December 28, 1941, graphite was included under General Imports Order M-63, which placed imports of critical materials under GovernTHE REPORT OF THE PARTY OF THE

<sup>&</sup>lt;sup>1</sup>Figures on imports and exports compiled by M. B. Price, of the Bureau of Mines, from records of the Department of Commerce.

ment control. On February 17, 1942, the War Production Board issued Order M-61, restricting the use of plus-35-mesh Madagascar flake graphite to the manufacture of crucibles, and named the Metals Reserve Co. as sole importer of graphite of this quality. On December 4, 1942, the order was amended to include all crystalline graphite (in flake, lump, or chip form) that will stand on a No. 50 mesh screen, U. S. Sieve Series. The United States depends principally on Madagascar and Ceylon for its supplies of strategic-grade graphite; therefore, imports in the following table are of primary importance.

Graphite (natural and artificial) imported into the United States for consumption, 1938-42

		Cryst	alline			Amorp	hous			
Year	Flake		Lump, chip, or dust		Natural		Artificial		Total (natural and artificial)	
	Short	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
1938	1, 620 2, 260 6, 551		209 602 752	\$13, 717 30, 421 54, 027	14, 676 18, 675 23, 766	269, 046	413	\$19, 870 15, 383 9, 187	17, 005 21, 950 31, 329	425, 326
1941: Australia Canada Ceylon Japan Madagascar	4,877	289, 322	(¹) 2, 705	16 363, 705 6, 492	839 10, 343 1, 853	53, 762 1, 072, 940 16, 439	38	1,384	(1) 877 13,048 1,853 5,071	16, 436, 645 16, 439 295, 814
Mexico United Kingdom			i	200	20, 347	220, 293			20, 347 1	,220, 293 200
	4,877	289, 322	2, 900	370, 413	33, 382	1, 363, 434	38	1, 384	41, 197	2, 024, 553
1942: Canada Ceylon China	7 280	2, 376 19, 098	3, 922 68	582, 928 9, 680	629 8, 951	36, 133 1, 157, 969	169	4, 739	68	43, 248 1, 759, 995 9, 680
India 2 Madagascar Mexico Union of South	5, 744	391, 445	56 106	3, 820 4, 722	23, 933	274, 476			56 5, 850 <b>23, 933</b>	3, 820 396, 167
Africa. United Kingdom 3					(1) 56	11, 500			(1) 56	11, 500
	6, 031	412, 919	4, 152	601, 150	33, 569	1, 480, 079	169	4, 739	43, 921	2, 498, 887

The Madagascar total of 5,850 short tons represents shipments received in March and April 1942, the only months of that year during which graphite arrived from the island. As a result of the allocation order of the War Production Board and its subsequent revision, the existing industrial and Government stocks of crucible flake on hand at the end of the year were adequate for current needs plus a 9-month reserve (3,600 short tons). The supply of Ceylon lump The supply of Ceylon lump material was in an even more favorable condition. Based on the quantity consumed during 1942 (800 short tons) and requirements estimated by the War Production Board for 1943 (900 short tons), the stock of 1,300 short tons at the end of 1942 represents a reserve of approximately 15 months' supply. Stocks of graphite fines represent a 2 years' supply.

Less than 1 ton.
 India and Dependencies (British India).
 United Kingdom of Great Britain and Northern Ireland.

Contract and and a second and a second

Exports of natural graphite, 1938–42, were—1938: 983 short tons, valued at \$112,443; 1939: 976 tons, \$109,715; 1940: 1,632 tons, \$148,639; 1941: 1,723 tons, \$166,612; and 1942: 4,420 tons, \$448,141.

Exports of natural graphite represent, for the most part, reexports of Madagascar flake; the export market includes U. S. S. R., England,

Canada, Mexico, and several South American countries.

As foreign shipments are uncertain, efforts were continued to promote a larger domestic output. The Bureau of Mines continued its investigation of possible domestic sources. Graphite samples from Alabama, Georgia, Pennsylvania, New York, Texas, and California were collected and analyzed. Various flow sheets were used in an attempt to determine the best method of recovery with minimum degradation of the coarse flake. The data from these tests were used as a guide in designing plants to produce crucible-grade flake graphite

approved by the War Production Board.

Five plants have been built with the assistance of loans from the Reconstruction Finance Corporation—three in Alabama and one each in Texas and Pennsylvania. They have a combined capacity of 4,300 short tons of crucible-grade graphite a year. Only one of the new plants was in operation during 1942, but all of them were producing by the end of the first quarter of 1943. The combined total of crystalline and amorphous graphite produced by domestic mines in 1942 was 7,070 short tons; except for part of the Ceylon Graphite Co. output, which sold as crucible flake, domestic graphite was used chiefly in foundry facings and paint. Artificial graphite was manufactured and sold by the Acheson Graphite Co., 30 East Forty-second Street, New York, N. Y., from a plant operated at Niagara Falls, N. Y.

The Canadian graphite industry is again becoming active as the result of a diamond-drill program by Ventures, Ltd., on the old Black Donald graphite property in eastern Ontario. Drilling has disclosed reserves of 40,000 tons of commercial-grade ore to a depth of 300 feet. The mill has been rehabilitated to treat 50 to 75 tons of ore daily.

Some impetus will be given to Mexican trade because of a trade treaty, signed December 23, 1942, which reduces the ad valorem duty on graphite from 10 percent to 5 percent. The treaty is effective for 3 years and thereafter until 6 months after either Government serves

notice of termination.

Prices for Madagascar and Ceylon graphite in carlots, f. o. b. New York City, duty paid, in 1942 were as follows, in cents per pound: Madagascar, No. 1 Flake, 9 to 16; No. 2 Flake, 7; Fines (ground), 55 to 70 percent carbon, 3; Ceylon Lump, 10 to 12; Carbon Lump, 9 to 10; Chip, 7; and Dust, 4 to 5.

Figures for total world production of graphite are not available. A table covering the period 1915-39 appeared in Minerals Yearbook, Review of 1940 (p. 1414), and the following table includes all produc-

tion figures from 1937 through 1942 that can be obtained.

World production of natural graphite, 1937-42, by countries, in metric tons 1 [Compiled by B. B. Waldbauer]

Country 1	1937	1938	1939	1940	1941	1942
ArgentinaAustralia:		28		100	135	(2)
New South Wales						18 94 82 2.
Queensland	12	10		63	64	3 91
South Australia	12	10		03	320	(2)
Tasmania				5	50	4 28
Brazil (exports)	9		(2)		5 60	(2)
Bulgaria			23	(2) 50		(2)
Canada (exports)	2, 675	1,044		1, 381	(2)	(2) (2) (2) (2)
Ceylon	5 17, 660	5 11, 972	5 22, 756	5 24, 414	(2) (2) (2) (2)	4 10 000
Chosen (exports)	43, 569	50, 348	78, 501	7 2, 591	8	6 10, 800
Czechoslovakia	5, 144	(2)	(2)		- X	(2) (2)
		(-)	, , ,	(2)	(2)	(2)
Jermany: Austria	18, 158	16, 852	2	(9)	(9)	(0)
Bavaria	23, 544	28, 106	(2)	8	127	(2)
Greenland		(2)	(2)	(2)	(2) (2) (2)	(2)
ndia, British	567	465	951	(2) (2) (2) (2) (2) (2) (2)	(2)	(2)
ndochina (exports)		100	931	(2)	(2) (2)	(2)
taly	5, 411	5, 485	(2)	(2)	(2)	(2)
Madagascar	5 12, 387	5 13. 432	2,70	15, 311		(2)
Mexico.	11, 210	9, 611		12, 327	13, 018	(2) (2) (2) (2) (2) (2) (2) 20, 816
Morogon		5, 011	9, 8, 5	12, 327	16, 928	20, 816
French (exports)	152	369	4 2	(9)	(9)	(0)
Spanish	102	73	(2)	<sup>(2)</sup> <sup>5</sup> 353	(2) 5 408	(2) (2)
Spanish	3, 638	3, 802	4,333			(2)
South-West Africa	3,000	3, 802	4, 555	(2) 71	(2) 188	(2) (2) (2)
weden	25	48	105	(2)	188	(2)
Union of South Africa	63	54	- 13	78	(2)	(*)
Inited States		04		18	(2) 8 62	8 656
Amorphous		(9)	(9)	(9)		
Crystalline	(9) (9)	(9) (9)	(9) (9)	(9)	(9) (9)	6, 414

<sup>&</sup>lt;sup>1</sup> In addition to countries listed graphite is produced in France, Japan, Nyasaland, Portuguese East Africa, Spain, and U. S. S. R., but production data are not available.

<sup>2</sup> Data not available.

3 January to July, inclusive. 4 January to June, inclusive.

Exports.
Estimated production.

April to December, inclusive.
January to October, inclusive.
Bureau of Mines not at liberty to publish figures.

## KYANITE, ANDALUSITE, AND DUMORTIERITE

Production of the sillimanite-group minerals increased in 1942 but not enough to keep pace with demand. The supply situation was aggravated by curtailment of shipments from India, occasioned partly by the threat of Japanese invasion of that country during the early months of 1942 and partly by lack of shipping facilities.

Domestic production, imports, and stocks of kyanite in the United States, 1940-42

Voor	Domestic produc- tion		Imports British	from India	Total 4e	w supply	Stocks 1		
1 tai	Short tons	Value	Short tons	Value	Shore tons	Value	Short	Value	
1940 1941 1942	4, 241 8, 335 8, 708	\$93, 716 175, 581 190, 750	7, 658 14, 285 6, 524	\$92, 159 175, 218 93, 743	11, 899 22, 620 15, 232	\$185, 875 350, 799 284, 493	(2) (2) (3 18, 970	(2) (2) 3 \$449, 317	

<sup>1</sup> Industry stocks of Indian kyanite as of Dec. 31.

<sup>&</sup>lt;sup>2</sup> Figures not available.
<sup>3</sup> War Production Board Miscellaneous Minerals Division.

The state of the s

Imports of Indian kyanite were received every month of 1942 but July and August. Although the proposed 1,500-ton Government stock pile had not materialized, industry stocks were still a year

ahead of the current requirement rate.

Domestic production of kyanite failed to attain expected proportions, chiefly because of dffiiculties in two eastern locations. Celo Mines, Inc., at Burnsville, N. C., pioneer producer in the east (which in 1941 became Mas-CeloMinnes, Inc., subsidiary of Munn & Steel of Newark, N. J.), ceased operation in June 1942; it was later reorganized as the Yancey Cyanite Co. and financed by the Reconstruction Finance Corporation. Mining and milling were resumed in February 1943 on a schedule of 12 tons of kyanite concentrate a day, or 300 tons a month. Half of this production will be low-iron glass-grade kyanite (Fe<sub>2</sub>O<sub>3</sub> content, not over 0.20 percent) and the remainder refractory grade. This company will do no calcining.

The Kyanite Products Corporation near Farmville, Va.—largest individual domestic producer—hampered by bad weather during the last quarter of the year and by loss of employees to the armed forces produced several the usand tons less in 1942 than capacity output. With an enlarged plant and stabilization of manpower, increased

production is expected during 1943.

Experimental works is still in progress to improve the grade of domestic kyanite, so that it may be used as a substitute for Indian kyanite. It makes an excellent mortar and may also be used in plastics, but at present it is not regarded as a satisfactory substitute

in superrefractories for the Indian material.

The cost of Indian kyanite delivered at Atlantic seaports rose from a little over \$30 per short ton in 1941 to \$54 in 1942. Prices for domestic kyanite have been set by the Office of Price Administration under Order MPR 327 released February 17, 1943. On and after that date domestic kyanite cannot be sold, delivered, or bought at a price above the highest net charged by the operator for the same product on a delivery made during March 1942.

Under this order specific prices were set for the Yancey Cyanite Co. (Asheville, N. C.) at \$22 per short ton f. o. b. plant for refractorygrade and \$40 for glass-grade material. Prices set for the Kyanite Products Corporation (11 Broadway, New York, N. Y.) were \$19 per short ton for raw kyanite, 35-mesh in carlots, to \$37.50 for 325-mesh material, less than carlots in 100-pound bags; for calcined kyanite in 100-pound bags, the range was \$26.50 per short ton, 35-mesh in carlots, to \$42.50 for 325-mesh material, less than carlots, f. o. b. Cullen or Pamplin, Va.

Production of andalusite on White Mountain, Mono County, Calif., and dumortierite at Oreana, Pershing County, Nev., by Champion Sillimanite, Inc., Merced, Calif.—only domestic producer of either mineral in 1942—increased sharply over the 1941 total. This material was shipped to the parent firm-Champion Spark Plug Co., Detroit, Mich.—for use in spark-plug cores and other electrical

porcelains. Experimental work on sillimanite from a deposit near Troy, Latah County, Idaho, indicates that the crude material must be beneficiated by flotation or a similar process of concentration to be marketable.2 A large deposit of sillimanite in the Broken Hill district, New South

<sup>&</sup>lt;sup>2</sup> Forrester, J. D., A Sillimanite Deposit Near Troy, Latah Co., Idaho: Idaho Bureau of Mines Pamph. 59, November 1942, 10 pp.

Wales, Australia, has been investigated by the Board of Economic Warfare through the War Supplies Procurement Mission of the Commonwealth of Australia. In January 1943 a 200-ton sample of this material was received in the United States by Charles F. Taylor & Sons Co., Cincinnati, Ohio, for use in experimental work in the manufacture of high-temperature refractories. If the tests are successful and shipping space is available a definite market can be developed for this material.

## LITHIUM MINERALS

Shipments of lithium minerals and compounds reached 5,405 short tons valued at \$243,516 in 1942 compared with 3,832 tons valued at \$115,718 in 1941; they originated in four States—South Dakota, North Carolina, California, and Maine. Lithium used as a scavenger in metal refining and as an alloy, the stearate in greases, the chloride in air-conditioning industrial plants and in dehydrating air in blast furnaces, and the hydride as a transporter of hydrogen have increased in importance during the war. Available production facilities were inadequate to meet these increasing demands. On December 5, 1942, the War Production Board promulgated Order M-253, placing all lithium ores under control of the Director General for Operations. This order includes not only ore produced on that date and thereafter but also stocks held within the continental limits of the United States as of that date, whether in private or Government hands. A much more favorable supply situation will be created in 1943 by the completion of the new plant of the Solvay Process Co. at Kings Mountain, N. C., and the rebuilding of the Black Hills Tin Co. mill at Tinton, S. Dak. (destroyed by fire January 5, 1943), and the entrance of several new producers into this field.

Under supervision of the War Production Board all new plants set up to produce and concentrate lithium ores were constructed to mill spodumene because of its relative abundance and ease of separation. Production is also confined to extraction of the chloride, to the exclu-

sion of other compounds which are used in ceramics.

The United States is the leading producer and consumer of lithium ores and compounds and apparently has the largest known ore reserves. South-West Africa, Australia, and Sweden produce the remainder of the world total, except for a small output from Canada, Portugal,

Southern Rhodesia, Spain, and Germany.

Information on world production of lithium ores has been meager since 1937, when the United States produced 52 percent of the world total, South-West Africa 42.5 percent, Portugal 4 percent, and other countries 1.5 percent. In pre-war times Germany produced about the same amount of lithium compounds as the United States; however, these were derived largely from ores imported, chiefly from the United States and South-West Africa. The present German position is therefore unfavorable, as the only sources of imports available to Germany are Sweden, Spain, and Portugal, which are minor producers. are not known but are probably small or nonexistent, as this mineral is usually mined as needed.

Prices for lithium ores produced in the United States for sale on the open market, as quoted by Engineering and Mining Journal Metal and Mineral Markets, were constant during 1942 as follows: \$5 per 20 pounds of contained lithia (Li<sub>2</sub>O), 6 percent minimum, relatively free of iron, quartz, and tourmaline, \$30 per short ton in carlots; amblyg-

一大大学 のでは、一大学のないではないというできません。 大学のないできる

onite, 8 to 9 percent Li<sub>2</sub>O, \$40 per short ton f. o. b. mine; and lepidolite, 3 percent (Li<sub>2</sub>O), \$24 to \$25 per short ton f. o. b. mine.

# MINERAL EARTH PIGMENTS AND MANUFACTURED IRON OXIDE PIGMENTS

[Prepared by Charles L. Harness]

World War II hastened domination of American markets by domestic pigments and encouraged local manufacture of many foreign-type pigments, thus accelerating trends in the earth-pigments industry that had been discernible for several years before 1939. Improvements in processing domestic pigments have offset without great difficulty the curtailment in imports of French yellow ochers, Spanish and Persian Gulf red iron oxides, Italian siennas, Turkish umbers, and German Vandyke and sap browns. Although the Bureau of Mines has no complete sales figures for mineral pigments in 1941 comparable with those for 1942, it estimates that total production was

30 percent greater in 1942 than in 1941.

Many producers geared their operations more closely to war needs in 1942. The Clinton Metallic Paint Co., Clinton, N. Y., formerly specializing in natural red iron oxide (Clinton hematite and blended colors based on it) for use in brick and mortar colors, installed equipment to prepare the pigments for paint use. To meet increased demands for earth pigments, the Geo. S. Mepham Corporation erected a new plant at East St. Louis, Ill. The Mineral Pigments Corporation, Muirkirk, Md., announced completion of new improved methods for synthesizing red iron oxides, Vandyke brown, and siennas; the siennas, which are made from scrap iron, are said to be considerably superior to Italian siennas. Reichard-Coulston, Inc., Bethlehem, Pa., built a plant for manufacturing synthetic yellow iron oxide for olive drab and camouflage paints. The Tamms Silica Co., Chicago, Ill., improved red iron oxides for use in rust-inhibiting primers and expanded its plant capacity for this and other products. C. K. Williams & Co., Easton, Pa., was active in camouflage-pigment research and was particularly successful in developing infrared-reflecting pigments.

Natural mineral pigments and manufactured iron oxide pigments sold by processors
— in the United States in 1942, by kinds

Pigment	Short tons	Value
Mineral blacks Precipitated magnetic blacks	2, 229 2, 244	\$83, 55 378, 39
Natural brown oxides (metallic browns)	7, 839 208	334, 44 27, 91
Pure browns (96 percent or better fron oxides)	17, 452	191, 24 863, 42 1, 551, 20
Pure red oxides (98 percent or better Fe <sub>2</sub> O <sub>3</sub> )  Venetian reds Other red iron oxides.	8, 507 5, 996	557, 57 518, 08
Natural yellow oxides (high Fe <sub>2</sub> O <sub>3</sub> )	8, 223 14, 426	228, 19 1, 963, 51 398, 82
Ochers (low Fe <sub>2</sub> O <sub>3</sub> )	12, 537 887	101, 60
BawUmbers:	2,358	309, 69
Burnt	2, 335 1, 146 695	140, 93 71, 18 44, 41
Other	97, 327	7, 764, 23

Natural mineral pigments and manufactured iron oxide pigments sold by processors in the United States in 1942, by States where processed

State where processed	Short tons	Value
Georgia Maryland Pennsylvania. Other States <sup>1</sup>	7, 067 2, 220 31, 815 56, 225	\$133, 111 147, 600 3, 142, 177 4, 341, 344
시간 : 레이스 이 발표 시간 시간 : 그리고 보기 : 15 등의 특별 연호생의 [15] 전 : 레인크로 인 기업의 - 등의 (15) 로드 (15) 및 (15)	97, 327	7, 764, 232

<sup>&</sup>lt;sup>1</sup> Arkansas, California, Illinois, New Jersey, New York, North Dakota, Ohio, Tennessee, Virginia, and Wisconsin.

Dry ocher, sienna, umber, and other forms of iron oxide for paint exported from the United States, 1939-42, by countries of destination

	19	39	19	40	19	41	1942		
Country of destina- tion	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	
Argentina Brazil Canada Colombia Cuba France	316 26 2,029 14 37 101	\$36, 377 3, 693 104, 519 2, 537 4, 721 6, 163	462 142 2, 691 22 45 24	\$57, 348 23, 397 133, 693 4, 275 6, 340 3, 258	325 243 3,006 124 172	\$44,906 35,319 200,427 24,751 21,872	50 108 2, 364 97 359	\$8, 993 22, 188 151, 109 26, 857 33, 681	
Mexico	69 101	9, 937 5, 554	122	24, 319	210	39, 411	153	32, 902	
Netherlands Indiès United Kingdom Venezuela Others	2, 328 30 320	3, 974 77, 596 3, 624 40, 594	82 1, 166 89 352	10, 182 33, 427 11, 563 39, 308	137 20 161 542	25, 099 8, 696 19, 264 72, 061	27 1 100 372	4, 830 224 16, 112 65, 761	
	5, 455	299, 289	5, 197	347, 110	4, 940	491, 806	3, 631	362, 657	

Selected mineral pigments imported into the United States for consumption, 1939-42, by kinds

	1	939	1	940	1	941	1942	
Pigment	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
Natural iron oxide Synthetic iron oxide Ocher, crude and refined Sienna, crude and refined	5, 439 3, 018 3, 465 1, 386	\$171, 649 305, 485 83, 560 74, 100	7, 451 2, 213 2, 099 815	\$248, 290 246, 898 52, 257 39, 740	6, 196 2, 321 380	\$232, 924 290, 162 11, 717	1, 936 1, 978 477	\$60, 697 250, 650 12, 036
Umber, crude and refined Vandyke brown	4, 727 453	57, 555 30, 555	2,826 7	43, 580	31 3	1, 579 185	(1)	159 43
	18, 488	722, 904	15, 411	631, 487	8, 931	536, 567	4, 396	323, 585

<sup>1</sup> Less than ½ ton.

Prices of finished earth pigments, which are quoted in cents per pound, were generally unchanged during the year, according to Oil, Paint and Drug Reporter. Precipitated magnetic blacks, in barrels, less carlots, works, were quoted at 8.5; metallic browns declined from 2.6 to 2.35; and Vandyke brown sold at 9, sap brown crystals at 12, synthetic browns at 12, natural red iron oxides at 2, synthetic red iron oxides at 9, Venetian reds at 2.2 to 4 (depending on iron oxide content), and natural yellow oxides, high iron, at 5. Synthetic iron oxide yellows declined from 7.25 to 7.1 during the year as production increased; domestic French-type ochers declined from 3.65 to

3.45; burnt siennas were quoted over a range of 3.5 to 6 (depending on quality), the prices declining slightly toward the end of the year; raw siennas ranged from 3.25 to 10, depending on quality, the quotations rising later in the year; and umbers were quoted at 3.375. Raw, untreated earth pigments are purchased by processors over a wide range of prices, from less than \$1 to as high as \$10 a ton at the mine.

#### MINERAL WOOL

The necessity of saving fuel for military uses, increasing the efficiency of industrial plants, and maintaining temperatures at normal levels in homes with less fuel during the war has hastened realization

of the true economy of insulation.

It is estimated that production of mineral wool in 1942 reached 500,000 short tons valued at \$22,500,000,3 representing production from 58 companies operating 70 plants. To meet the unusual demands, the industry operated virtually at capacity, and this capacity was enlarged substantially by improvement in melting technique, which increased the output of mineral wool per ton of fuel from 2 to 1 to about 4 to 1 as an average, with a maximum of 6 to 1 in several plants. Efforts are being made to stabilize employment in the industry by encouraging dealers to purchase on a monthly basis rather than seasonally and thus keep production and employment in constant balance.

Through the efforts of the National Bureau of Standards and the Industrial Mineral Wool Institute, commercial specifications for the use of mineral wool in loose, granulated, or felted form in low-temperature installations were established in December 1942, to be effective on and after March 1, 1943. Tests at the National Bureau of Standards in Washington, D. C., the Engineering Experiment Station of the University of Illinois, and the National Research Council of Canada, as described in a recent Bureau of Mines information circular, show that complete insulation of homes results in a 30-percent

saving in fuel consumption.

This fuel saving is particularly important to the eastern region, which contains 65 percent of the total oil burners installed in the United States. The Office of Price Administration estimates that

51 percent of the houses having oil burners are insulated.

Mineral-wool insulation has been specified for use in military equipment by the War and Navy Departments for tanks, airplanes, and bulkhead insulation in ships. The loss of life by fire and suffocation from fumes of burning-cork insulation in sinking ships during the Pearl Harbor attack was responsible in large measure for the change in specifications for ship insulation. Prices in 1942, per short ton in carlots, f. o. b. plant, were \$30 for loose mineral wool and \$45 for granulated wool.

#### MONAZITE

Monazite sand is the only commercial source of cerium, other rareearth oxides, and thorium which, although used in rather small quantities, are essential to many industries. The United States

<sup>3</sup> Estimate by Bureau of Mines, based on figures obtained from War Production Board covering first half of 1942,
4 Bowles, Oliver, Home Insulation with Mineral Products—Conservation of Fuel for War: Bureau of Mines Inf. Circ. 7220, 1942, 15 pp.

depends entirely upon British India and Brazil for its supplies. Imports of monazite sands in 1942 increased 950 short tons over 1941. and the tonnage received from Brazil represented 31 percent of the total in 1942 as against 21 percent in 1941. If need be, Brazilian production can be expanded to supply all our essential requirements. The stock pile of these sands—entirely in the hands of industry—is in excellent condition, containing 21/2 years' supply at the current rate of consumption as of March 1943.

Monazite sand and other thorium ore imported into the United States for consumption, 1938-42, by countries of origin 1

	1938			1939		1940		1941	1942	
Country of origin	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value	Short tons	Value
Brazil India and Dependencies <sup>2</sup> Netherlands Indies	110 339	\$3, 421 14, 402	54 1, 336 170	\$1, 516 46, 753 3, 747	201 2, 766	\$7, 440 92, 387	734 2, 714	\$25, 240 82, 068	1, 346 3, 052	\$62, 555 112, 928
United Kingdom 3	7	387								
	456	18, 210	1, 560	52, 016	2, 967	99, 827	3, 448	107, 308	4, 398	175, 483

1 Quantities are gross weight; monazite content not reported.

<sup>2</sup> British India. <sup>3</sup> Great Britain and Northern Ireland.

Commercial utilization of the various elements in monazite sand has expanded considerably in the past few years. The original basis of value of 6 to 8 percent thoria content has been superseded by the ceria and other rare-earth oxides content, and requirements are now based on a 57- to 60-percent minimum of rare-earth oxides. Considerable technical skill is required to extract the rare-earth metals from these sands, and for many purposes the rare earths are used as a group. Cerium and the cerium group—the most important rare-earth elements—are used principally as arc stabilizers in carbon arc lamps, as mildew-proofing agents, and in the manufacture of pyrophoric Thorium is used principally in electron-emissive elements, praseodymium and neodymium are used in the manufacture of special optical glasses, and lanthanum and erbium in beauty preparations.

The market for these sands is variable and sporadic; therefore, buyers' specifications are elastic. Indian sands are finer-grained and have a higher thoria content than those of Brazil. The following quoted prices are nominal: \$42.50 per long ton f. o. b. India plus \$24 ocean freight to Baltimore; and \$64 per metric ton f. o. b. Brazil plus \$17 ocean freight to Baltimore.

#### OLIVINE

Shipments of olivine reached 5,739 short tons valued at \$45,201 in 1942 and were consumed entirely in refractories. This tonnage is the largest ever produced and shipped in the United States. Olivine occurs in commercial quantities only in the rock dunite and in its alteration products, serpentine and steatite. These rocks, in lump or ground form, make up the material produced and sold as olivine.

Olivine deposits are found chiefly in Washington, California, North Carolina, and Georgia. A review of these deposits, which includes an estimate of their reserves and a description of their development in the past few years, has recently been published.<sup>5</sup> Of particular interest is the experimental work now in progress to determine the potentiali-

ties of olivine as an ore of magnesium.

Prices for crude olivine, f. o. b. North Carolina, were quoted at \$7 to \$9 per short ton, and for ground olivine, 8- to 200-mesh, at \$12 to \$20 per short ton.

#### QUARTZ CRYSTAL

Piezoelectric-grade quartz crystals, which are required for radio oscillators and filters, telephone resonators, and other sound equipment, head the list of strategic and critical minerals published by the War Production Board. Although several domestic sources of supply bear some promise, we still depend upon Brazil for quartz of this grade, and the question as to whether our supply from Brazil will be adequate to meet the present requirement rate depends upon the extent to which small crystals can be used.

Imports of quartz pebbles reached 1,305 short tons valued at \$8,941,965 in 1942. Except for imports of 1,024 pounds from Guatemala and 61 pounds from Colombia, which were sample shipments, the entire quantity was received from Brazil. This tonnage supplied 5,202,808 small <sup>6</sup> oscillators, 1,576,782 large <sup>6</sup> oscillators, 91,173 tele-

phone resonators, and 17,050 units for detection equipment.

However, much of the quartz received did not meet specifications, and more thorough, systematic check of the material in Brazil was begun. American engineers were sent to visit the various producing areas, and inspection laboratories were set up in Rio de Janeiro. Toward the close of 1942 production increased, and quality improved.

Toward the close of 1942 production increased, and quality improved. On May 18, 1942, the War Production Board under Order M-146 assumed control over the products for which quartz crystals may be used; and on August 4, 1942, under General Imports Order M-63, importers were required to obtain War Production Board authorization for disposal of quartz crystals in this country. Beginning in January 1943 most of the crystals imported into the United States were air-borne, arriving at New York City, Washington, D. C., and Miami, Fla.; the largest portion entered at the Florida port. Only the low-grade material (of which about 10 percent will be usable) will be brought in by ships, and it will be purchased entirely by the Metals Reserve Co.

Arkansas, California, and certain other areas in the United States offer possibilities for developing domestic quartz-crystal production. The Hot Springs area in Arkansas offers two good possibilities, each of which (it is believed) will yield about 50 tons a year of 30-percent-usable material. Samples of Arkansas quartz when tested show a higher piezoelectric activity than Brazilian material.

Complete specifications and prices for piezoelectric-grade quartz have not been formulated, chiefly because of the lack of a systematic and consistent method of mining and grading the material at the source. The original specifications called for quartz, each piece weighing not less than 200 grams, 30 percent or more of which must

<sup>&</sup>lt;sup>5</sup> Gwinn, G. Richards, Olivine: Bureau of Mines Inf. Circ. 7239, 1943, 11 pp.
<sup>6</sup> "Small" defined as one-half inch or smaller in January-April and October-December 1942; as five-eighths inch or smaller in May-September.
"Large" defined as sizes above these in same periods.

be free from inclusions, cracks, needles, bubbles, or twinning. Because of improved technique developed under the urge of necessity, smaller crystals were subsequently accepted. The minimum size has been reduced in several stages until in March 1943 it stood at 50 grams.

## STRONTIUM MINERALS

[Prepared by Charles L. Harness]

Sales of celestite (crude strontium sulfate) by domestic producers declined somewhat, amounting to 4,041 short tons valued at \$55,529 in 1942, compared with 4,724 tons valued at \$69,054 in 1941. Despite an active market for use in tracer bullets and flares, no new deposits of chemical-grade celestite were worked commercially in 1942. Production of the abundant subchemical-grade celestite in Texas, formerly used entirely for oil-well drilling muds, declined with curtailment in drilling activity, although some of the higher-grade rock was sold for purifying caustic soda and for conversion to strontium chemicals, both with and without beneficiation. Research by the Bureau of Mines and by the Foote Mineral Co. on methods of beneficiating crude celestite found in Brown and Nolan Counties, Tex., indicated that the impure celestite can be beneficiated to a plus-92-percent content of strontium sulfate.

Imports of celestite into the United States amounted to 10,387 short tons valued at \$144,848 in 1942, mostly from Mexico, compared with 4,294 tons valued at \$66,271 in 1941, mostly from the United Kingdom.

Prices for chemical-grade celestite, lump, ranged from \$30 to \$35

a short ton laid down in the Philadelphia area.

#### TOPAZ

The United Feldspar & Minerals Corporation, of Spruce Pine, N. C., shipped 583 short tons of topaz valued at \$8,807 from the Brewer mine near Kershaw, S. C., in 1942; it was used entirely in refractories. Experiments are still being made by the Bureau of Mines regarding the substitution of properly calcined topaz or a product composed of domestic kyanite and topaz for Indian kyanite in refractories.

#### VERMICULITE

Sales of crude and exfoliated vermiculite, which originated in seven States, totaled 57,848 short tons valued at \$319,931 in 1942. Production was more than twice that in 1941, when 23,438 tons valued at \$125,444 were sold. Although the Universal Zonolite Insulation Co. (2601 West One Hundred and Seventh Street, Chicago, Ill.), operating properties at Libby, Mont., remained the predominant producer and processor, the number of smaller producers increased during 1942.

The increased production of this material is directly associated with wartime industries. Under normal trade conditions the principal use for expanded vermiculite has been in home insulation, a minor portion being employed in acoustical installation, lightweight plaster, cements, and coatings. However, during the war major uses of expanded vermiculite have been as an aggregate in lightweight and insulating concretes—principally in poured concrete for structural roof deck—

and in insulating roof and floor fills in temporary and permanent buildings. Vermiculite is also employed in deck coverings and firewalls of tankers that may be exposed to bombing attacks and by the petroleum industry for lining cracking units in refineries where vermiculite blocks or bricks serve both as refractories and insulators.

Virtually all vermiculite that enters the domestic market is cleaned and screened at the mine; some is exfoliated by the producers, or it may be sold to a processor for exfoliation. Screened vermiculite was sold to processors at \$8 to \$12 a short ton f. o. b. mine. The exfoliated material was quoted at 70 cents to \$1.25 a bag—each bag containing 4 cubic feet weighing 25 pounds—or \$56 to \$100 a short ton f. o. b.

works.



## PART IV. MINE SAFETY

# EMPLOYMENT AND ACCIDENTS IN THE MINERAL INDUSTRIES

By W. W. Adams

#### SUMMARY OUTLINE

	Page		Page
Introduction	1539	Employment and accidents—Continued.	4
Employment and accidents	1542	Traprock quarries	1546
Bituminous-coal mines	1542	Granite quarries	1546
Anthracite mines	1543	Sandstone quarries	1547
Iron-ore mines		Limestone quarries	1547
Copper mines	1544	Limekilns and associated quarries	1547
Lead and zinc mines (Mississippi Valley States).		Byproduct coke ovens	1547
Gold and silver mines (lode and placer)	1544	Beehive coke ovens	1547
Miscellaneous metal mines		Ore-dressing plants	
Nonmetallic-mineral mines		Smelters	1548
Cement mills and quarries		Auxiliary works at ore-dressing plants and	
Marble quarries		smelters	1548
Clate quarries		Summary, 1932–42	1548

## INTRODUCTION

The war year 1942 witnessed the operation of the mining industry of the United States with somewhat fewer men employed but with a large increase in number of man-hours of work performed. Copper, iron, lead, zinc, and other metals were in great demand by the Army and Navy; they were needed also for the manufacture of tools and other working equipment by civilian industrial plants engaged in producing airplanes, guns, tanks, and ships for the armed forces. Thus, the metal-mining industry was the original source of supply of raw materials of war. Back of the industries whose raw materials were of metal stood the coal-mining industry, without whose product the metal-using industries could not operate and the transportation systems of the Nation could not function. Faced with such conditions in 1942, the metal-mining industry and the coal-mining industry measured up to their wartime responsibilities. The difficult situation was met, so far as the mining and allied industries are concerned, by extension of the period of operation over a larger number of days during the year rather than by an attempt to increase the number of employees in the face of ever-increasing calls for men by the armed forces.

Reports thus far received (many companies not having yet reported) indicate that the mines, quarries, coke ovens, ore-dressing plants, and smelters in the United States employed approximately 812,600 men in 1942, or about 23,000 less than in 1941. However, operations during 1942, expressed in man-days of labor performed, reached nearly 211 million, a gain of 15 million man-days over the previous year. Expressed in another way, the volume of work performed was about 1.6 billion man-hours, compared with approximately 1.4 billion during 1941.

1539

Accidents to the employees caused 1,878 deaths and 97,232 nonfatal lost-time injuries, such an injury meaning one that disables an employee longer than the remainder of the day on which he is hurt.

Based upon reports received by the Bureau, the mineral industries may be grouped into 22 classes, as shown in the accompanying table. Of these classes, 14 were operated with fewer employees than in 1941 As the number of employees, however, does not and 8 with more. necessarily indicate the extent of operations, the number of man-hours of work by the employees must be considered; on this basis, 15 classes showed gains and 7 showed losses. Of special note among the branches of the mineral industry that increased the number of man-hours of work during 1942 were mines and quarries or other plants that produced coal, iron, copper, lead and zinc, cement, limestone, coke, and such metals as mercury, manganese, and tungsten (included under "Miscellaneous" metals in the table). Gold mining experienced a loss in both number of employees and of man-hours worked, owing to the order of the War Production Board, which stopped or greatly reduced operations at mines whose principal output was gold-bearing ores.

Number of men employed 1 in the mineral industries of the United States, 1940-42

	1940	1941	1942 2
Coal mines:			
Bituminous	440.045	455 505	
Pennsylvania anthracite	440,847	457, 737	449,000
Temsylvania anomacite	92, 420	88, 948	83, 500
	533, 267	546, 685	532, 500
	=====	010,000	002, 000
Metal mines: Iron	12.		
iron	23, 250	25, 870	28, 100
Lead-zinc (Mississippi Valley)	7,644	8, 634	8,800
(!Onner	19, 498	21, 576	22,600
Gold and silver lode mines (including lead, zinc, and copper,	1	21,010	22,000
except as listed above)	39, 128	38, 235	29,900
Gold placer mines	15, 701	13, 368	12,700
Miscellaneous (tungsten, manganese, etc.)	5, 119	6,614	
Company management of the contract of the cont	0, 119	0, 014	7,000
	110, 340	114, 297	109, 100
Nonmetallic-mineral mines	9,780	11, 088	10, 900
	0,700	11,000	10, 900
Quarries:			
Cement	26, 695	28, 859	30, 200
Marble	3, 240	2, 693	
Slate	2, 800		2,400
Traprock	2, 951	2,845	2,400
Granite	-, -, -, -	3,029	2,900
Sandstone		7,830	6, 500
Timestone		3, 180	3, 100
Limestone	23, 251	26, 395	25, 900
Lime	10, 332	11, 292	10, 500
	79, 509	86, 123	83, 900
Coke ovens:			
Byproduct	17 400	40.000	
Beehive		18, 633	19, 500
Deemve	2, 493	4,008	4, 300
	19, 962	22, 641	23, 800
	=====	22,011	20,000
Metallurgical plants:			
Mills	13, 990	14,807	14,900
Smelters.	20, 120	22,003	20, 700
Auxiliary works	14, 958	17, 539	16,800
	<u>-</u>		
	49, 068	54, 349	52, 400
Grand total	901 000	005 100	010.655
	801, 926	835, 183	812, 600
	1		

<sup>&</sup>lt;sup>1</sup> Figures represent summation of reports for individual mines showing daily average number of employees at each mine on days when mine was in operation
<sup>2</sup> Subject to revision.

An 11-year (1932 to 1942) review of accidents and employment in the 22 classes of the mineral industries of the United States is presented in the following table. Trend lines based upon the figures in the table are given in figure 1. As is evident from the table, the volume of employment, as measured by number of man-hours worked,




FIGURE 1.—Trend of employment and fatal and nonfatal accidents in the mineral industries of the United States, 1933—42.

reached its maximum in 1942. Maximum employment, as measured by the number of men working without regard to the number of days or hours available, was reached in 1937. The frequency of accidents in relation to the volume of employment in 1942, though not at the lowest point during the 11-year period, compared favorably with all other years except 1941.

Employment and accident record of mineral industries of the United States, 1932-42

Year	Men em-	Man-days of employment	Man-hours of employment	Nu	mber		er million -hours
				Killed	Injured	Killed	Injured
1932 1933 1934 1935 1936 1937 1938 1939 1940 1941	671, 343 677, 722 739, 817 783, 139 824, 514 859, 951 774, 894 788, 925 801, 926 835, 183 812, 600	110, 655, 616 122, 787, 658 144, 566, 133 152, 354, 170 177, 920, 334 186, 790, 283 145, 056, 875 159, 388, 490 175, 663, 792 195, 425, 228 210, 778, 000	900, 211, 723 984, 570, 160 1, 081, 694, 716 1, 128, 808, 465 1, 326, 347, 029 1, 381, 261, 415 1, 069, 729, 725 1, 169, 331, 497 1, 293, 131, 693 1, 440, 988, 174 1, 550, 206, 000	1, 368 1, 242 1, 429 1, 495 1, 686 1, 759 1, 369 1, 334 1, 716 1, 622 1, 878	68, 717 72, 342 81, 660 82, 219 92, 644 96, 484 71, 618 75, 495 82, 861 90, 334 97, 232	1. 52 1. 26 1. 32 1. 32 1. 27 1. 27 1. 28 1. 14 1. 33 1. 13 1. 20	76. 33 73. 48 75. 49 72. 84 69. 85 66. 95 64. 56 64. 08 62. 69 62. 72

<sup>1</sup> Subject to revision.

# EMPLOYMENT AND ACCIDENTS

# BITUMINOUS-COAL MINES

Employment.—More than 775 million man-hours of labor and a working force of about 449,000 men were required to operate the bituminous-coal mines of the United States during 1942. Production of coal reached 579 million short tons, or 12 percent more than in 1941; it exceeded the production of each year in the history of coal mining in the United States with the possible exception of 1918, the previous record year. About 2 percent fewer men worked in 1942 than in 1941, but the number of man-hours worked increased 12 per-The large increase in production was the direct result of the heavy demand for coal for the industries of a nation at war, as bituminous coal is predominantly an industrial fuel and is the chief source of power on which other industries depend. The greater demand for coal was met with a smaller working force than in 1941 owing to the transfer of many coal-mine workers to the armed forces and, perhaps to a less extent, to the attraction of some employees to nonmining industries.

Accidents.—Accidents at the mines during 1942, according to present reports, killed 1,254 employees. This number, if confirmed by final reports, will indicate an increase of 182 over the number of miners killed in 1941. Nonfatal injuries increased by more than 7,400 and reached a total estimated at 54,125. The accident rate per million man-hours of employment during 1942 now stands at 1.62 for fatalities (slightly above 1941) and at 69.84 for nonfatal injuries, the latter rate being comparable with the previous year's rate of 67.49.

The year was marked by 6 major disasters in which 127 men were killed, as compared with 8 such disasters in 1941 when 73 men lost their lives. The six major disasters of 1942 were chargeable to four States—one each to Arkansas, Colorado, and Kentucky and three to West Virginia—and all were explosions.

Detailed information as to the causes of the more than 55,000 injuries and deaths in 1942 are not yet available and will not be known for several months, when reports from all mines in the United States shall have been received. However, a review of accident records over a period of years affords a typical picture of the cause-distribution of fatal and nonfatal injuries at bituminous-coal mines. For example,

during the 5-year period 1936 to 1940 accidents caused 5,247 deaths and 222,693 nonfatal lost-time injuries among the employees, a total of 227,940 personal injuries. Following are the percentages of the total number of accidents due to each main cause.

TI- James and a said onta	Percent
Underground accidents: Falls of roof or face	27.8
Mine cars and locomotives	22. 1
Handling materials	13. 5
Uand tools	7. 0
Machinery (cutters, loaders, etc.)	7. 3
Falls of persons	J. 0
Fundations of res or coal dust	. 0
ExplosivesExplosives	. 7 1. 5
Hilootricity	1. 0
Miscellaneous	0.0
Shaft accidents	2. 6
Open-pit-mine accidents	6. 2
Surface accidents	
	100. 0

A similar distribution of fatal accidents alone, which comprise only 2 or 3 percent of the large number of accidents, would show a different percentage distribution. The main causes of fatal accidents, in order of their numerical importance, are falls of roof or face, haulage accidents, gas and dust explosions, electricity, and machinery, these five classes covering about 88 percent of the total number of fatal accidents during any representative period in recent years.

## ANTHRACITE MINES

Employment.—The output from mines of eastern Pennsylvania constitutes the product known as "anthracite" or "hard coal." Although a few other localities of the United States also produce hard coal, anthracite is usually identified with the coal-mining industry of eastern Pennsylvania. During 1942 the mines of this region produced and prepared for market approximately 58 million short tons of coal. This does not include several million tons from illegitimate or so-called bootleg mines, as reports of accidents or employment from such mines are not available. The regular or legitimate anthracite industry employed 83,500 men in 1942, according to reports available at present. These men worked approximately 144 million hours in and about the mines, breakers, preparation plants, washeries, and strip pits. Seven hours was the standard shift. Preliminary returns indicate that the collieries were operated about 246 days during the year, or 39 days more than in 1941.

Accidents.—Fatal accidents occurred to 228 men, an increase of 34 over the number reported for 1941. The number of nonfatal injuries increased also, the estimate for 1942 being 17,500, compared with 16,828 reported for the previous year. In relation to the increased man-hours of work, the record for 1942 was favorable, as the injury rate was 121.53, a decrease from 129.34 for 1941. The fatality rate

for 1942 stands at 1.58, compared with 1.49 for 1941.

No major disasters have occurred in the anthracite mines of Pennsylvania since June 2, 1938, when an explosion of gas in a mine in Luzerne County caused the loss of 10 lives. This disaster-free record represents a period of 1,673 days to December 31, 1942.

### IRON-ORE MINES

Employment.—Men employed and man-hours worked increased sharply in 1942. Incomplete returns indicate a total of 28,100 employees, a gain of nearly 9 percent over the year 1941. The total manhours worked during the year was nearly 65 million, an increase of approximately 18 percent over 1941 when 54.9 million man-hours of work was performed.

Accidents.—Notwithstanding an increase in men employed and manhours worked, continued progress was made in accident prevention. The accident-frequency rate was 22.69 per million man-hours in 1942, which compares favorably with the rate of 23.07 for 1941. The estimated number of injuries during 1942 is 1,466, including 51 fatalities.

### COPPER MINES

Employment.—The demand for copper, due to the war, caused an increase in employment beyond that recorded in 1941, which was already substantially above the volume of employment in 1940. The number of mine workers reached approximately 22,600, an increase of 5 percent over 1941 and of 16 percent over 1940. Similarly, the number of man-hours of labor worked at the mines rose to about 58.8 million in 1942, from 55.1 million in 1941 and 48.7 million in 1940.

Accidents.—With increased employment and, hence, greater exposure to mining hazards, accidents in 1942 might also be expected to increase in number. However, present reports indicate no increase in the number for that year and an actual reduction in the accident rate per million man-hours worked. Both the fatality rate and the injury rate appear to have declined in 1942. Present information indicates a fatality rate of 0.83 and an injury rate of 49.99, compared with 1.14 and 53.71, respectively, in 1941.

# LEAD AND ZINC MINES (MISSISSIPPI VALLEY STATES)

Classification.—This group covers mines producing lead and zinc in the Mississippi Valley States, chiefly Oklahoma, Missouri, and Kansas, and those producing fluorspar in Kentucky and Illinois, where somewhat comparable conditions prevail.

Employment.—The number of men working increased slightly in 1942, and the number of man-hours showed a decided gain. The number of employees was approximately 8,800, a gain of 2 percent. The aggregate man-hours worked increased about 13 percent, as preliminary reports for the year indicated 19.2 million man-hours worked compared with 16.9 million in 1941.

Accidents.—Tentative figures now available reveal that accidents increased in 1942 and resulted in a higher accident-frequency rate than in 1941. The accident rate increased from 59.35 per million man-hours in 1941 to approximately 65.81 in 1942. The safety record, therefore, was less favorable than in 1941. Accidents during 1942 caused 17 deaths and 1,247 injuries.

# GOLD AND SILVER MINES (LODE AND PLACER)

Classification.—This group includes mines operated chiefly for the gold or silver content of their ores; it also includes mines outside the Mississippi Valley region whose ores were valuable mainly for the lead or zinc they contained, as well as mines that produced some copper

but whose ores were chiefly valuable for metals other than copper.

Both placer mines and lode mines are included in the group.

Employment.—Employment diminished in volume in 1942, particularly during the latter part of the year, following the order of the War Production Board requiring the closing of many mines engaged chiefly in the production of gold. From a total of 51,603 employees in 1941, reports thus far received (for 1942) indicate about 42,600 men employed. Man-hours of work dropped from 90 million in 1941 to approximately 69 million in 1942.

Accidents.—According to present reports, accidents caused 85 deaths and 6,464 nonfatal injuries during 1942, representing a fatality rate of 1.24 and an injury rate of 94.33 per million man-hours worked, as compared with a fatality rate of 0.81 and an injury rate of 92.00 in 1941. Eight deaths were caused by a single disaster at a mine in

Colorado.

## MISCELLANEOUS METAL MINES

Classification.—This group includes all mines engaged in production of metallic ores exclusive of gold, silver, copper, lead, zinc, and iron. It therefore includes mines that produced such critical and strategic metallic ores (ores declared essential to the national defense) as bauxite, chromite, manganese, mercury, molybdenum, and tungsten, as well as various other minerals.

Employment.—Preliminary figures now available reveal that the production demands of a war economy have been partly responsible for raising employment in 1942 to approximately 7,000 men, or 6 percent over 1941. Man-hours of employment rose to over 15.1 million in 1942, compared with 13.8 million in 1941, or approximately 10 per-

cent.

Accidents.—As estimated for 1942, the safety record was more favorable than that of 1941. The accident-frequency rate per million man-hours of employment was 81.30, compared with 85.03 for 1941. Present reports indicate that 17 men were killed and 1,213 injured by accidents in 1942.

## NONMETALLIC-MINERAL MINES

Classification.—Included in this group are mines that yield any kind of nonmetallic mineral except coal, stone, sand, gravel, and clay. Hence, it includes all those that produce barite, feldspar, gypsum, sulfur, rock salt, mica, phosphate rock, and many other minerals.

Employment.—Employment in 1941 numbered 11,088 men, and in 1942, according to preliminary figures, the group as a whole employed approximately 10,900 men. The man-hours of employment, however, rose to 24.1 million, compared with 23.2 in 1941, or about 4

Accidents.—From reports now available for 1942, the accident-frequency rate was about 50.55 per million man-hours, which represents progress when compared with the 1941 rate of 51.62. Accidents during 1942 resulted in 19 deaths and 1,196 injuries among the workers.

## CEMENT MILLS AND QUARRIES

Employment.—Approximately 30,200 men were employed in the cement industry (quarrying and manufacturing) during 1942, an increase of 5 percent over 1941. These men worked about 72 million man-hours, which was 11 percent more than in 1941.

Accidents.—Increased employment in 1942 was accompanied by an increase in the number of fatal and nonfatal accidents. It is estimated that 46 men lost their lives during the year, including 28 who were killed in a single disaster caused by an explosion of dynamite; nonfatal injuries are estimated at 797. The fatality rate was 0.64 and the nonfatal-injury rate 11.10, compared with final rates of 0.22 and 10.93, respectively, in 1941.

## MARBLE QUARRIES

Employment.—Employment at marble quarries and related plants in the United States continued to decrease in 1942. Employment is estimated at 2,400 men and 4.9 million man-hours, a decline from 2,693 men and 5.2 million man-hours for 1941. The proportionate decrease in number of man-hours of employment during 1942 was not as great as that in number of employees, hence an increase in number of days of employment per man.

Accidents.—Two men were killed by accidents, whereas no deaths were reported in 1941. The fatality rate for 1942 is estimated at 0.41 per million man-hours of exposure. Nonfatal injuries, estimated at 212, give a rate of 42.95, compared with a final rate of 46.33 for 1941.

## SLATE QUARRIES

Employment.—Preliminary estimates indicate a decrease of approximately 16 percent in number of men employed in 1942. Employment expressed in man-hours was 4.8 million for the 2,400 men employed.

Accidents.—Two men were killed and 439 injured by accidents.

The number of injuries was much larger than for 1941, when only 323 occurred. Based on these estimates, the fatality rate for 1942 was 0.42 and the nonfatal-injury rate was 91.14 per million man-hours, compared with 0.18 and 57.21, respectively, based on final figures for 1941.

# TRAPROCK QUARRIES

Employment.—Preliminary reports indicate about 2,900 employees and 5.3 million man-hours worked in 1942. Employment in 1941 covered 3,029 men and slightly less than 5.3 million man-hours.

Accidents.—Accidents resulted in 5 fatalities and 256 nonfatal injuries, according to incomplete reports. These figures represent a fatality rate of 0.94 and an injury rate of 48.07 per million man-hours of employment and indicate a relatively large reduction in accident frequency.

### GRANITE QUARRIES

Employment.—The estimated number of employees was 6,500, a decrease of 17 percent from the 1941 total. These men worked 1.5 million man-shifts or 12.7 million man-hours during the year. The decline in employment was due chiefly to the shut-down or curtailment of operations at dimension-stone plants and quarries.

Accidents.—Estimates indicate that 15 men were killed by accidents. This record compares unfavorably with that of 1941, which showed only 8 fatalities. Nonfatal injuries declined along with the decrease in employment, the number of such injuries having been 610, according to available data. Accidents in 1942 gave a fatality rate of 1.18 and a nonfatal-injury rate of 47.84 per million man-hours of employment; the rates for 1941 were 0.55 and 49.40, respectively.

### SANDSTONE QUARRIES

Employment - Employment changed very little in 1942 from 1941; estimates place the number of workers at 3,100, with a total of 5.7 million man-hours worked. As the number of man-hours decreased 3 percent, compared with the 1941 total, and the number of men employed was virtually unchanged, the working time per man declined

Accidents.—Accidents in and about quarries and related plants resulted in death to 2 men and in lost-time injuries to an additional 336 men. Neither the fatality nor injury rate changed materially from 1941, when the record showed 0.34 and 59.76, respectively.

# LIMESTONE QUARRIES

Employment.-Incomplete reports indicate that the number of men employed was about 25,900, a decline of 2 percent from 1941. However, the number of man-hours of employment increased 4 percent. Final returns for 1942 are expected to show a total of 48.7 million

man-hours of work performed during the year.

Accidents.—Thirty men were killed and 2,540 men injured in accidents during the year. This is a decrease in nonfatal accidents from 1941, when 2,622 men were injured; however, the number of fatalities remained the same as in 1941. Thus, the fatality rate for 1942 was 0.62 compared with 0.64 for 1941, and the nonfatal-injury rate was 52.16 compared with 55.96.

# LIMEKILNS AND ASSOCIATED QUARRIES

Employment.—The number of men employed, estimated at 10,500, was 7 percent less than the number employed in 1941. Despite this decrease, the number of man-hours of employment was 25.2 million, virtually the same as in 1941. Thus, the average employee had a longer work year—304 days or 2,400 hours; comparable figures for 1941 are 296 and 2,241, respectively.

Accidents.—Fortunately, the number of both fatal and nonfatal accidents declined substantially in 1942. Estimates indicate that 10 men were killed and 1,460 injured, compared with 17 and 1,551, respectively, in 1941. The 1942 fatality rate was 0.40 and the nonfatal-injury rate was 57.94, compared with a fatality rate of 0.67 and

a nonfatal-injury rate of 61.30 in 1941.

## BYPRODUCT COKE OVENS

Employment.—Final figures on employment during 1942 show 19,551 men employed, or 5 percent more than in 1941. They worked 56,771,172 man-hours, or 2,904 hours per man, during the year; manhours of employment also increased 5 percent over 1941.

Accidents.—Accidents occurring among the employees killed 9 men and injured 545 during 1942. These accidents represent a fatality rate of 0.16 and a nonfatal-injury rate of 9.60 per million man-hours of employment, compared with 0.22 and 8.07, respectively, in 1941.

## BEEHIVE COKE OVENS

Employment.—Present estimates indicate that employment in 1942 reached a new high level for recent years. Final returns are expected to show that 4,300 men were employed for a total of 8.5 million manhours.

Accidents.—Three men were killed and 375 men met with lost-time injuries from accidents during the year. These accidents indicate a fatality rate of 0.35 and a nonfatal-injury rate of 44.04 per million man-hours of employment. If these rates are unchanged by final returns they will be lower than the fatality rate of 0.43 and nonfatal-injury rate of 52.71 for the beehive-coke industry in 1941.

### ORE-DRESSING PLANTS

Employment.—Gains in the number of workers and the man-hours worked in 1942, compared with 1941, were reported by ore-dressing and beneficiating plants. Men employed numbered about 14,900 and approximately 36 million man-hours of work was performed.

Accidents.—Incomplete data indicate an accident-frequency rate of 27.09 per million man-hours in 1942. As this rate is lower than the rate of 28.42 in 1941, the safety record for 1942 appears slightly more favorable than that of the previous year.

### SMELTERS

Employment.—Included in the term "smelters," as used herein, are operations employed in the smelting and refining of all metallic ores other than iron ore. The smelting of iron ore and manufacture of steel are not included in the accident and employment statistics collected by the Bureau of Mines, as such statistics are collected and tabulated by the Department of Labor. Reports for the smelting industry indicate that 20,700 men were employed in 1942. This represents a loss of 6 percent in number of employees from 1941 but a gain of 3 percent over 1940. The man-hours of employment increased 3 percent, however, being 56 million in 1942.

Accidents.—The intense production effort occasioned by war demands resulted in a setback to accident prevention for the third successive year. The accident-frequency rate rose in 1942 to 30.49,

from 27.05 in 1941, 19.70 in 1940, and 16.35 in 1939.

# AUXILIARY WORKS AT ORE-DRESSING PLANTS AND SMELTERS

Employment.—All operations at mills and smelters not directly connected with milling and smelting processes are included in the term "auxiliary works." About 16,800 men were employed in such works in 1942, a decrease of 4 percent from 1941. Despite this loss in number of employees, man-hours worked increased about 4 percent, reaching 44.8 million.

Accidents.—The accident-frequency rate for 1942 increased slightly, being 20.65 per million man-hours compared with 20.06 in 1941.

## SUMMARY, 1932-42

Absenteeism has become widely recognized as a factor in the slowing down of production of war materials. Also widely recognized are certain contributions to absenteeism. Among these are insufficiency of supplies when needed, inadequacy of transportation facilities, strikes, lock-outs, sickness, and accidents. Perhaps accidents are least widely recognized as contributors; and perhaps even less appreciated, not only by the public but by many production experts, is

that saboteur of war energy, the preventable accident. Although all will agree that some risk of personal injury is inherent, or seemingly inherent, in industry, there can be no justification or excuse, even

in wartime, for most of the accidents that occur.


On several recent occasions the attention of the public and of industry has been called by the President of the United States to the importance of conserving manpower through the prevention of accidents in factories, on farms, in mines, and on the highways and railways of the country. It has become conventional to recite some of the leading causes of these accidents. The public has to some extent become familiar with such recitals. To safety engineers they are an old story. But perhaps it may justly be said that the chief cause of all accidents in the mineral and other industries is the small amount or complete absence of thought given to the importance of accident prevention by those who do not have safety thrust upon their attention every day. To such persons, in many instances, the safety engineer must look for the approval and support of his safety programs. Until the safety engineer occupies a position in his organization equal to and not under that of the production engineer, industrial workers will continue to be killed and injured by preventable accidents, and the rehabilitation of needlessly injured persons will remain a major and serious problem demanding the attention of governmental and other agencies.

In 1942, a year in which the Nation could ill afford a loss of manpower from any cause, between 3 and 4 million man-days were lost because of accidents in the mineral industries alone. This loss was from injuries classed as "temporary", so called because in each instance the injured employee was ultimately able to return to work without having lost a leg, foot, arm, or other part of his body. A loss of manpower nearly as great arose from injuries classed as "permanent injuries", as the accident caused the loss of some part of the body or of its use. Such cases are considered equivalent to the loss of 6,000 work days when they permanently and totally incapacitate

Applying this thought to the coal-mining industry alone it may be observed that as the over-all average of production of coal in the United States is about 4.9 tons per man per day, the loss of time from "temporary" injuries alone represented a production loss of 15 or 20 million tons of coal during 1942. An additional and even larger loss, not confined to 1942, must be charged for deaths and permanenttotal and permanent-partial disabilities caused by accidents. losses are continuing, owing to the permanent impairment of the miner's ability to work and, in the case of deaths or permanent-total disability, owing to the absolute cessation of the miner's ability to produce coal.

In the face of such losses, which are but a repetition of a record that has continued for many years, there can be little doubt that one of the most important problems facing the Nation is the prevention of industrial accidents. It is to be hoped that when the war is won, the safeguarding of the lives and limbs of industrial workers will be advanced to the front ranks among subjects universally recognized as meriting first consideration of production engineers and executives

of industry.



# By MABEL E. WINSLOW

A Page	Page
Abrasives, artificial, review 1345	Alumina abrasives, review1342
sales 1345	Aluminum, foreign trade 685, 686, 702
sales	primary, consumption699
metallic, sales 1345, 1346	Aluminum, foreign trade 685, 686, 702 primary, consumption 699 prices 700 Office of Price Administration schedule 700
Abrasive industries, annual review 1331	production 695 698 605
Accidents, mineral industries, annual data 9,1539	production 685, 686, 695 priorities, mandatory 704 production, capacity 697 resources, National Academy of Sciences
Acid phosphates, exports1378 Africa. See Algeria; Belgian Congo; Cyprus;	production, capacity 697
French Cameroun; French Morocco;	resources, National Academy of Sciences
Gold Coast; Liberia; Madagascar;	
Morocco; Nigeria; North Africa; Rho-	secondary, annual review   522   consumption   523,700   foreign trade   525
desia, Northern; Rhodesia, Southern; South-West Africa; Tunisia; Union	foreign trade
South-West Africa; Tunisia; Union	prices 525
of South Africa.	price control 525
Agalmatolite, deposits 1390 Air furnaces, ferrous scrap and pig iron, con-	recovery 521, 522, 685, 686, 699
sumotion552, 559	stocks524
Alabama, bauxite, deposits, Geological Sur-	technologic developments 703
vey and Bureau of Mines investiga-	Aluminum chloride, data693 Aluminum Co. of America, Government suit
tions 689	against 698
needuction 699	Aluminum industry, annual review 695
bituminous-coal industry, data 837, 852, 853, 854, 869, 870, 871, 875, 876, 880, 881,	Government expansion program 696
882, 883, 886, 889.	labor data697
gold production 85 97 101 351 353 355	war measures
iron ore, review 580, 586, 591	Aluminum oxide, saies 1345, 1346 Aluminum plants, Government-owned 685
manganese ore, data	lime-soda-sinter units. War Production
iron ore, review 580, 586, 591 manganese ore, data. 616, 617, 618 minerals, production 43, 45, 48, 49 Alaska, antimony, data 784	lime-soda-sinter units, War Production Board approval 696 Aleminum salts, production 693
Alaska, antimony, data 784	Aleminum salts, production 693
bituminous-coal industry, data 837,853,	shipments 693 Aluminum scrap. See Aluminum, secondary.
856, 858, 863, 864, 869, 889	Aluminum scrap. See Aluminum, secondary.
Cook Inlet-Susitna region, mining industry 223	Aluminum sulfate, anhydrous, production method
Copper River region, mining industry 223	data693
gold, production 85, 97, 99, 101, 102, 103, 220, 222	Alunite, as source of notash, Bureau of Mines
gold dredges, list 104	investigations 1454
copper, production	investigations 1454 Amethyst, production 1512 Ammonia, allocation 1523 production 956, 992, 995, 996, 1000
Kenai Peninsula region, mining industry 224	Ammonia, allocation 1523
Kuskokwim region, mining industry 224 lead, production 169, 220, 221	production 956, 992, 995, 996, 1000 sales 1000
mercury, data 721	synthetic, production 1523
mercury, data 721 deposits, Bureau of Mines investi-	uses
gations715, 716	Ammonium nitrate, imports 1524
metals, production. annual review 219	uses1524
metallurgic industry, review 222 minerals, production 43, 45, 48, 49	Ammonium sulfate, allocation, War Produc- tion Board 954
molybdenum, deposits, Bureau of Mines	tion Board 954 byproduct, allocation 1523
and Geological Survey investigations 661	l sales
Northwestern region, mining industry 224	Amosite, restriction, War Production Board
ores, markets222	conservation order 1424
Seward Peninsula region, mining industry 224	uses1424
silver, production 85, 97, 99, 101, 102, 103, 220, 222 Southeastern region, mining industry 225 tin, deposits, Bureau of Mines and Geological Survey investigations 736	in block insulation 1428 Amphibole asbestos. See Asbestos.
tin deposits. Bureau of Mines and Geo-	Andalusite, production
logical Survey investigations 736	Anthophyllite, deposits 1424
tungsten, data	Anthracite, "bootleg", production 925
deposits, Bureau of Mines and Geological	competitive fuels 841, 842, 843
Survey investigations 674 Yukon River Basin region, mining industry 228	consumption 921, 924 definition 914
	definition 914
	foreign trade 915.931.947
asbestos, deposit1434 mercury, data727	freight rates 931
titanium-zirconium concentrates, produc-	loading, mechanical 944
tion817	machine cutting, status 945
Allocation control. See War Production	1914   1915   1916   1917
Board.	production 857 915 932 935 936 937
Alloy-steel castings, manufacture 608	sales realization 915. 926. 940
Alum, data 693	salient statistics 915
Alumina, Bureau of Mines investigations 703	sales realization       915, 926, 940         salient statistics       915         shipments       923, 924, 938
data	stocks
production, capacity697 sources, clay1328	supplies 922 transportation 922
sources, clay 1328 lime-soda-sinter method 1329	warktatus
TOPO	

Page	Page
Anthracite breakers, culm-bank coal put	Arizona, metallurgic industry, review 238
through 937	minerals, production 43, 45, 48, 50
Anthracite Coal Commission, Federal, report Anthracite fields, description 935	mining industry, review 237
Anthracite Industries, Inc., research 914, 919	Mohave County, metals, production 236, 237, 239, 240, 241, 242, 244, 251
Anthracite industry, annual review 913	ore, classification 238
dredging operations 947	Pima County, metals, production 236,
dredging operations         947           labor data         920, 942           problems, research         913	237, 240, 241, 242, 244, 252 Pinal County, metals, production 236,
Voluntary Production-Control Plan 919	240, 241, 242, 244, 253
Anthracite Institute, activities 919	Santa Cruz County, metals, production 236.
Anthracite mines, accidents 1543 days worked 943	237, 239, 240, 241, 242, 245, 255
mechanization 944	silver, production 85, 95, 97, 98, 99, 101, 102, 103, 232, 233, 234, 236, 237, 238, 239, 240, 241, 242,
mechanization944 men employed915, 926, 942, 943, 1540, 1543	243.
Anthracite regions, description 935 research laboratory, authorization 920	tungsten, data676 vanadium, deposits667
research laboratory, authorization 920 Anthracite stokers, sales, restrictions 931	wulfenite, deposit, as source of molybdenum 661
Anthracite strip pits, expansion 946	Yavapai County, metals, production 236, 237, 239, 240, 241, 242, 245, 255
Anthracite Tidewater Emergency Bureau, functions 914	237, 239, 240, 241, 242, 245, 255 Yuma County, metals, production 236,
Antimonial lead, foreign trade 175 production 166, 167, 782, 786 Antimony, as reagent, in glass manufacture 758	237, 239, 240, 241, 242, 246, 258
production 166, 167, 782, 786	zinc, production189,
Antimony, as reagent, in glass manufacture 758 consumption	233, 235, 236, 238, 239, 240, 241, 242, 243 Arkansas, bauxite, deposits, Geological Survey
Matels Pasarva Co contracts 26	and Bureau of Mines investigations 689
needle, foreign trade 789	hituminous-coal industry, data 837 852 853
prices	856, 858, 863, 864, 869, 870, 871, 875, 876 881, 882, 883, 890.
primary, production, mine 781, 782, 784	lead, production 169, 297, 298, 299
18	manganese ore data 616 617 618
reclassification, by War Production Board. 783 resale, Metals Reserve Co	mercury, data 720, 721
salient statistics 782	minerals, production 43, 45, 48, 50
salient statistics 782 secondary, annual review 539	metals, production, annual review 29 minerals, production 43, 45, 48, 50 natural gas, data 1131, 1132, 1133, 1134, 1150,
prices	1151, 1152, 1154, 1157
price control 540 priority control 540 recovery 521, 539, 782, 787	petroleum industry, data 1036, 1037, 1033, 1039, 1060, 1064, 1065, 1068, 1070, 1071, 1095, 1096,
recovery521, 539, 782, 787	1100, 1106.
stock pile 781	quartz crystals, deposits 1512
regulation, by war agencies 783	rutile, data
Antimony industry, annual review 781 regulation, by war agencies 783 Antimony metal, foreign trade 789, 790 Antimony ore, foreign trade 782, 786, 789, 790	Army Air Forces, fluorspar plants, protection 1393
import licenses 783	Army-Navy Munitions Board, stock-pile pur- chases25
Antimony oxides, foreign trade 789	Army Service Forces, copper, savings
Antimony scrap. See Antimony, secondary.  Apatite, foreign trade	Arsenic, allocation control 577 producers, list 755
Apatite, foreign trade 1375 Apatite-ilmenite ore, deposit 1373	producers, list
Aplite, extinguishing incendiary bombs with. 1420	uses 757
production 1419	white, consumption 755, 757 foreign trade 755, 756
uses 1419 Argentina, antimony, data 791, 792	prices 759
beryl, data 821	production 755
fluorspar, data	sales       756         stocks       759
lead, data	world prospects 759
mica, data1472, 1474, 1475	Arsenic compounds, price control
tin, data 746, 749 tungsten, data 681, 683, 684	Arsenic industry, annual review 755 Arsenic trichloride, uses 758
zinc, data	Arsphenamines, for treatment of syphillis,
zinc, data 198, 199, 200 Arizona, asbestos, review 1425 bituminous-coal industry, data 853,	sales         758           Asbestos, amphibole, production         1425
858, 863, 864, 869, 889	sales 1425
Cochise County, metals, production 239,	uses 1424
240, 241, 242, 243, 247 Coconino County, metals, production 242, 243, 248	characteristics, advantages 1423 chrysotile, production 1425
copper, production 135, 136, 137,	sales1425
138, 139, 233, 235, 236, 238, 239, 240, 241, 242, 243	uses 1423, 1424
fluorspar industry, review 1399 Gila County, metals, production 241 242 243 248	consumption, trends         1426           domestic deposits, type         1424
Gila County, metals, production 241, 242, 243, 248 gold, production 85,	foreign trade 1429
95, 97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116,	markets 1427
117, 232, 233, 236, 237, 238, 239, 240, 241, 242, 243	prices1428 sales1425
gold producers, list 93 Graham County, metals, production 236, 242, 243, 249	goliont statistics 1495
242, 243, 249	use, to replace critical metals 1428
Greenlee County, metals, production 236, 237, 241, 242, 243, 249	use, to replace critical metals. 1428 Asbestos fiber, Metals Reserve Co., purchases 1424 Asbestos-graphite product, uses 1428
indiam sine ore deposit containing 925	Aspestos industry, annual review
iron ore, data587, 591	Asbestos products, foreign trade
iron ore, data. 587, 591 lead, production 169, 232, 236, 238, 239, 240, 241, 242, 243 manganese ore, data. 616, 617, 618	Ash, volcanic, uses
manganese ore, data616, 617, 618	Burma; Ceylon; China; Japan; Johore;
Maricopa County, metals, production 236, 237, 239, 240, 241, 242, 243, 250 mercury, data 720, 721	Malay States, Unfederated; Manchuria;
mercury, data 720, 721, 242, 243, 250	Turkey: Union of Socialist Soviet

Page	Page
Asphalt, cut-back, sales 1188, 1189	Belgian Congo, abrasive diamonds, foreign
distribution 1190	trade1343 cadmium, production797, 800
foreign trade 1185, 1190 native, prices 1185	cadmium, production 797, 800
native, prices 1185	cobalt, review       654         copper, review       154, 155
sales	tontolite date
Asphalt industry, annual review 1185	tantalite, data 824 tin, data 28, 746, 747, 749 Bentonite, prices 1323
	Bentonite, prices 1323
arsenic, white, data 760	sales
bauxite, data 705, 706	salient statistics 1316
copper, review 154, 155	uses 1323
gold, data120, 126	uses 1323 Bentonite industry, annual review 1323 Benzol, allocation, War Production Board 954
lead, data	Benzol, allocation, War Production Board 954
Asstrain, authorly, data 760 bauxite, data 760, 705, 706 copper, review 154, 155 gold, data 120, 126 lead, data 174, 175, 177 magnesite, data 1496 magnesium data 778	price control
magnesium, data 778 mica, data 1474, 1475 New South Wales, sillimanite deposit,	Beryl, foreign trade
Morr South Woles cillimenite denocit	shipments 819
Board of Economic Warfare investi-	stocks 820
gation 1529	Bervllium, annual review 819
gation 1529 pyrites, data 1361 tin, data 746, 747, 749	production 819
tin, data	uses 821 Beryllium-copper alloys, manufacture 820
titanium concentrates, production 817 i	Beryllium-copper alloys, manufacture 820
	prices820
Western, blue asbestos, data 1428, 1433	uses 821 Beryllium ore, deposit, Bureau of Mines and
zine dete 250estos, uata102 100 100	Geological Survey investigations 819
chrysotile asbestos, data 1433 zinc, data 198, 199, 200 Automobiles, use, regulation, by Office of	prospecting for 819
Price Administration 1085	Bessemer converters, ferrous scrap and pig
Aviation gasoline, production program 1092	iron, consumption 552, 556
	iron, consumption 552, 556 Bessemer steel, manufacture 609
<b>B</b>	Rismuth, consumption 764
	foreign trade         764           producers, list         763
Bahamas, magnesia, data 1496	producers, list 763 production 763
Ball clay, imports 1320	production 763 stock piles, Metals Reserve Co 765
prices       1320         sales       1317, 1321         salient statistics       1316	uses 764
salient statistics 1316	Bismuth compounds, prices 765
war uses 1320	uses 765
war uses1320 Ball-clay industry, annual review1320	Bismuth industry, annual review
Barite, crude, prices 1436, 1438	Bismuth metal, prices 765
production 1436 sales 1436, 1437, 1438	Bitumens, foreign trade 1190
sales 1436, 1437, 1438	sulfonated, sales 1185 Bituminous coal, cleaning, mechanical 832, 883
ground, prices 1442 sales 1436, 1440	competition from other sources of energy 834,
uses	839. 842. 843
college statistics 1436	839, 842, 843 consumption 831, 838
Barite industry, annual review 1435, 1436	distribution 832, 844
Barium carbonate, foreign trade 1446	foreign trade 907
prices1446	fuel efficiency       838, 842         loaded for shipment       864         production       831, 835, 836, 837, 852, 853, 855, 856
production 1445 war uses 1445	108ded for Shipment 201 025 026 027 059 052 055 056
war uses1445 Barium chemicals, foreign trade1436, 1446	922
nrices 1446	sales       922         salient statistics       835         stocks       832, 846
prices 1446 sales 1436, 1443	stocks832,846
salient statistics	value, average860
Barium chloride, foreign trade 1446	Bituminous-coal industry, annual review 831
prices1446	capacity     832       labor data     832, 861       trends     847, 848, 850
uses 1445 Barium dioxide, foreign trade 1446	18.00° Gata
prices 1446	Bituminous-coal mines, accidents 1542
Barium hydroxide, foreign trade	
uses1445	mechanization, data 832, 870
Barium nitrate, foreign trade	mechanization, data 832, 870 men employed 832, 835, 848, 850, 853, 861, 1540, 1542 mining methods 859
prices1446	mining methods 869
uses1445	number         858           power drilling         876
Barium oxide, foreign trade       1446         Barium products industry, annual review       1435, 1443         Basalt, crushed, sales       122, 1225, 1226, 1228         1222, 1225, 1226, 1228	power drilling 870 size 858
Recalt emiched color 1943 1944	stating sugmentions and look outs 940 964
sales 1222, 1225, 1226, 1228	stringing operations 871
Bateman-Juarez-Tellez agreement, for pur-	working day 862
chase of lead from Mexico 178	Bituminous rock, prices 1185
Battery ore, shipments 616, 627	sales1185
Bauxite, consumption 686, 690 deposits, Coastal Plain, Midway-Wilcox	Strikes, Suspensions, and rock-outs
deposits, Coastal Plain, Midway-Wilcox	foreign trade 1446 Blast furnaces, consumption, ferrous scrap and
contact 689 foreign trade 686, 691, 695, 696	pig iron
prices 694	number 599
priorities 705	number 599 Blue asbestos, deposits 1428, 1431, 1432, 1433
priorities 705 production 686, 687	foreign trade1431
shipments686, 688	uses     1424       Blue clay, imports     1316, 1320
stocks 690 stock pile, Metals Reserve Co 690	Directors selections and the selection of the selection o
stock pile, Metals Reserve Co	Rolivia antimony data 781 791 792
Bauxite industry, annual review 687 Bayer process, red-mud tailings, treatment, by	Bluestone, sales 1235 Bolivia, antimony, data 781, 791, 792 blue asbestos, deposit 1433
lime-soda-sinter method, to obtain	copper, data153, 156
alumina 703	lead, data
Beach sands, as source of chromite, mineral	copper, data. 153, 156 lead, data 174, 178 sulfur, data 187 tin, data. 28, 731, 733, 741, 749
dressing, Bureau of Mines study 637	tin, data 28, 731, 733, 741, 749

병원 회사 기가 되었다. 경기 회사 기가 가지 않는 것 같다.	Page	1	Page
Bolivia, tungsten, data 681, 68	3, 684	Bureau of Mines, investigations, strategic	J- 7.
zinc, data		minerals, copper	130
lead	131 165	magnesium maganese	1500
metals	22	mercury deposits	613 714
_ zinc	182	molybdenum deposits	661
Borates, annual review	1507	nickel deposits	646
Borax, price producers, list	1508 1507	tintungsten	735
sales	1507	tale	674 1386
uses	1508	manganese manufactured by, for Bureau of	1000
Boron, annual review	821	Mint	614
uses. Boron minerals, salient statistics.	821	metanurgical tests, cobait	652
uses	1507 1508	monthly canvasses, asbestos molybdenum	1424 661
Brass, secondary, analysis	528	organization	19
annual review	526	organization process, for recovering lithium chloride from	
consumption foreign trade	529 531	spodumene	1502
prices	530	surveys, chromite consumption fluorspar	638 1391
price control	530	war activities	18
recovery	526	Burkeite, as source of sodium carbonate	1505
Brass scrap. See Brass, secondary.	1949	Burma, lead, data 177	
Brazil, abrasive diamonds, foreign trade	1343	nephrite jade, deposits ruby, mining methods	1519
asbestos products, proposed manufacture	1433	tin, data 746	1518 $750$
beryl, data	821	l zinc data	201
chromite, data	640	Burrstones, foreign trade Butane, sales 1172, Butane-propane mixtures, sales 1172,	1348
cobalt, datafluorspar, data	654 1409	Butane, sales 1172,	1175
gem stones, exports	1519	Dutane-propane mixtures, sales 11/2,	1170
gold, data 119	, 125	σ	
lead, data 176	3, 178		
magnesite, data manganese ore, data	620	Cadmium, consumption	798
manganese ore, data1472, 1474,	1475	foreign trade	797
nickel, data648	3, 649	prices	799
	1535	price control priority control	799
rutile, production817 tantalite-columbite, data	7,818 824	producers, list	795 796
zinc, data198		production	795
Brick, building, data	1328	salient statistics	795
	1354	stocksCadmium compounds, production	799 797
Brine, salt content	1480	Cadmium industry, annual review.	795
British Guiana, bauxite, data 705 British India, antimony, data 791	707	world aspects	800
hauxite review 705	5 700 1	Calcium, annual review	822
manganese ore, data mica, review 1472, 1473, 1474,	629	production Calcium arsenate, use, as insecticide	822 757
mica, review	1475		1502
titanium ores, production 817 British Malaya, tin, data 746, 747	. 818 1	prices	1503
Bromine, annual review	1503	producers, list	1502
prices	1504		1501 1502
pricesproducers, list	1503		1502
salesuses_	1503 1503	sales	1501
Building, nonessential, stoppage by War Pro-	1909	Calcium metal, foreign trade	822
duction Board conservation order	1283	Calcium-silicon, foreign trade	822
Building construction, record rate	205	California, Alpine County, metals, produc- tion 267, 272	276
Building stone, sales 1222, 1223, 1224, Bulgaria, chromite, data 640	1226	tion267, 272 Amador County, metals, production	267,
Bureau of Mines, anthracite experiment sta-	, 641	272, 273, 274, 275, 276	, 282
tion, authorization by Congress	920	andalusite, production	1529
cooperation, with Office of Solid Fuels Co-	1	antimony, dataasbestos, production	784 1426
ordination for War	913	barite, production	1442
electrolytic process, for manganese exploration, phosphate rock deposits, as	614	Butte County, metals, production	267,
source of vanadium	668	272, 273, 274, 276	
grinding tests, carnotite ores	826	070 079 074 075 076	267,
investigations, alunite, as source of potash	1454	272, 273, 274, 275, 276	634
cobalt-nickel concentrates graphite, domestic sources	646 1527	copper, production 135, 136.	137.
magnesium	776	138, 139, 263, 266, 268, 271, 272, 273, 274, 275	, 276
magnesium well, as source of notash	ļ	copper, production 135, 136, 138, 139, 263, 266, 268, 271, 272, 273, 274, 275, Del Norte County, metals, production 267	, 276
salts	1455	Eldorado County, metals, production 272, 273, 274, 275, 276	004
	776	fluorspar, data 1399,	1400
from olivine	777	Fresno County, metals, production 267, 276.	. 284
from olivine recovery of vanadium from ilmenite	- 1	Fresno County, metals, production 267, 276, gold, production	85,
tanings	816	95, 97, 98, 99, 101, 102, 103, 106, 109, 111, 113, 116, 117, 263, 267, 271, 272, 273, 274, 275, 276.	115,
slate, waste, as aggregate strategic minerals	1262	210, 117, 205, 207, 271, 272, 273, 274, 275, 276.	105
alumina	703	gold dredges, list93,	. 265
bauxiteberyllium ore, deposit	689	gold mines, leading 93, Humboldt County, metals, production 275,	267,
beryllium ore, deposit	819	275,	, 276
chromite	637	Imperial County, metals, production	267,

Page	Page
alifornia, Inyo County, metals, production 267,	Canada, asbestos, review 1429, 1430, 1431 barite, data 1439, 1440 bauxite, data 777, 800 chromite, data 777, 800 chromite, data 640, 641 chrysotile, data 1423, 1424 coal industry, review 153, 156 ferrous scrap, review 564 fluorspar, data 1407, 1408, 1409 gem stones, review 151, 152 gold, review 119, 122 graphite industry 1527 ilmenite, data 817, 818 indium, production 825 lead, review 174, 176, 177, 178 lime, foreign trade 1313 magnesia, data 1472, 1473, 1474 molybdenum, review 662, 663 nepheline syenite, production 1418 nickel industry, review 645, 646, 648, 649 pig iron, production 565 pigments industry, data 207 pitchblende mine, reopening 827 radium, review 809 pyrites, data 130 radium, review 809 pyrites, data 130 radium, review 809 pyrites, data 130 radium, review 809 pyrites, data 130 radium, review 809 pyrites, data 1366, 137 radium, review 826, 837 stalc, review 1390 tantalite, data 824 tin, review 1390 tantalite, data 681, 683, 684 vanadium, review 669, 670 War Supplies, Ltd., agreement with Metals Reserve Co. 20 Richem 198, 199, 200, 201
272, 273, 274, 275, 277, 285 iron ore, data	bauxite, data707
Kern County, metals, production 267, 272, 274, 275, 277, 285	cadmium, data797, 800
272, 274, 275, 277, 285	chrysotile data
lead, production 169,	coal industry, review 947
lead, production 169, 170, 263, 267, 268, 271, 272, 273, 274, 275, 276  Los Angeles County, metals, production 267,	copper, review153, 156
Los Angeles County, metals, production 267, 272, 273, 274, 275, 277, 286	ferrous scrap, review564
Madera County, metals, production 287, 275, 277, 287 magnesium products, data 1494 manganese ore, data 616, 617, 618	fluorspar, data 1407, 1408, 1409
272, 275, 277, 287	gem stones, review 119 122
magnesium products, data616 617 618	graphite industry 1527
Mariposa County, metals, production 267, 272, 273, 274, 275, 277, 287	ilmenite, data 817, 818
272, 273, 274, 275, 277, 287	indium, production825
Merced County, metals, production 267, 277, 288	lead, review
Merced County, metals, production 267, 277, 288 mercury, data 720, 721 deposits, Bureau of Mines and Geological	magnesia data
Survey explorations 715	magnesium, review 776, 778
261	mercury, data713, 727
metallurgic industry, review 271 minerals, production 43, 45, 48, 51 mining industry, review 289 mining industry, review 987	mica, data
minerals, production 43, 45, 48, 51	molybdenum, review 662, 663
mining industry, review209	nickel industry, review 645, 646, 648, 649
mining industry, review	nig iron production 565
natural gas, review1128,	pigments industry, data207
1131, 1132, 1133, 1134, 1135, 1150, 1151, 1152, 1154	pitchblende mine, reopening 827
natural gas, review	platinum metals, recovery
	radium review 826.827
Nevada County, metals, production 267, 272, 273, 274, 275, 278, 288 Orange County, metals, production 267, 272, 274, 275, 278, 288	silver, review 121, 122
Orange County, metals, production 267,	soapstone, ground, review 1390
273, 274, 275, 278, 288	steatite, deposits
ore, classification. 270 petroleum industry, data. 1036, 1036, 1037, 1038, 1039, 1060, 1064, 1065, 1068, 1070, 1071, 1095, 1096, 1100, 1106, 1107, 1109, 1110  Places County models production 267.	tolo review 1390
petroleum industry, data	tantalite, data 824
1071, 1095, 1096, 1100, 1106, 1107, 1109, 1110	tin, review 747, 750
	tungsten, data681, 683, 684
212, 213, 214, 210, 210, 200	Vanadium, review 009, 070
Plumas County, metals, production 267,	War Supplies, Ltd., agreement with Metals Reserve Co
notesh review 1449, 1452	zinc, review198, 199, 200, 201
pyrites, data1359	Capaco process, description 1293
Plumas County, metals, production 207, 272, 273, 274, 275, 278, 290 potash, review 1449, 1452 pyrites, data 1359 Riverside County, metals, production 267, 273, 275, 278	Reserve Co
	deliveries 1181
Sacramento County, metals, production 267, 279, 290	demand1181
San Bernardino County, metals, produc- tion 267, 273, 274, 275, 279, 290	foreign trade1178, 1183
tion267, 273, 274, 275, 279, 290	manufacture, natural gas, consumption 1128,
San Diego County, metals, production 267, 273, 279	prices 1184
San Francisco County, metals, production 267, 279	manufacture, natural gas, consumption
San Joaquin County, metals, production 267, 279, 291	production1178, 1179
	salient statistics
San Luis Obispo County, metals, produc- tion267, 279	value 1178, 1184
Santa Barbara County, metals, production 267,	
	Carbon-black plants, natural gas used 1180
scheelite, data	
Shasta County, metals, production 267, 272, 273, 274, 275, 279, 291	1525
Shasta County, metals, production 272, 273, 274, 275, 279, 291  Sierra County, metals, production 267, 272, 274, 279, 292	Carnotite, production 826
272, 274, 279, 292	Carnotite ores, as source of variadium
silver, production 85, 95, 97, 98, 99, 101, 102, 103,	Bureau of Mines grinding tests 826 Casein, for paints, allocation control 206
263, 268, 271, 272, 273, 274, 275, 270	Casein, for paints, allocation control 206 Casey bill, suspending tariff on scrap 546
silver mines, leading 94, 266 Siskiyou County, metals, production 267, 268	Celestite, foreign trade 1536
272, 273, 274, 275, 280, 292	sales1536
sodium sulfates, data 1505	Celler bill, to remove restrictions on silver 84
272, 273, 274, 275, 280, 292 sodium sulfates, data	Cement, consumption 1203 foreign trade 1217 prices 1210
sulfur, deposit 1352	prices1210
Trinity County, metals, production 267, 272, 273, 274, 275, 280, 293	price control, Office of Price Administration 1190
272, 273, 274, 275, 280, 293	production 1193, 1194, 1197, 1198, 1200, 1218
Tulare County, metals, production267, 272, 274, 280, 293	salient statistics 1194 shipments 1194, 1197, 1198, 1200, 1205, 1206
tungston review 676 677	I stocks 1(44-1198-120)
tungsten mine, as source of molybdenum 660	supplies 1208
Tuolumne County, metals, production 267,	supplies 1208 transportation 1208 Cement industry, annual review 1193
Tuolumne County, metals, production 267, 272, 273, 274, 275, 280, 293	Cement industry, annual review
Yuba County, metals, production 267, 272, 280, 294	
gine production 189, 263.	Cement plants, capacity 1211
960 971 979 972 974 975 976	men employed 1540, 1546 Cement plants, capacity 1211 Central America, bauxite, deposits 708
Canada, aluminum, review	See also Costa Rica; Honduras; Nicaragus.
anthracite, imports947	126 127 120 120 006 907 906
ersenic data 760	gold, production296
carron, and december of the second	. •

Page	
Central States, lead, production_169, 170, 296, 297, 298	Page
metals, production, annual review295	Coke, furnace, production 978
metallitrgic industry review 900	gas-house, production 99
mining industry, review	metallurgical, research 95
mining industry, review 298 silver, production 85, 97, 101, 296, 297 zinc, production 189, 296, 297, 298	price 98: salient statistics 955, 957
zinc, production189, 296, 297, 298	shient statistics 955, 957
Cerium, annual review 823	stocks 956, 986
as reagent, in glass manufacture 758	
foreign trade823	value 92
uses 1534	value 92. See also Petroleum coke.
Cerium metal, prices cos	Coke breeze, production 976
Ceylon, mica, data1474, 1475	stocks 981
Unite, copper, increased production, financing	yield 976
by Defense Plant Corporation29	Coke byproducts, annual review 993
review 153, 157	Coke industry, annual review 951
gold, data 119, 125 manganese ore, data 629	Government control 953
manganese ore, data629	Uoke manufacture, fuel efficiency
potassium-sodium nitrate, foreign trade 1522	Coke ovens, beehive, accidents
sodium nitrate, foreign trade1522	Coke ovens, beehive, accidents 1547 men employed 1540, 1547
Chine olyminass material 3.56, 1357	byproduct, accidents 1547
ontimony data 708	capacityg67
tin review 991,793	men employed 1540, 1547 owned by city gas companies 1001
sulfur, data	owned by city gas companies 1001
nrices 1320	coal charged       967,969         heating, new method       955         number       965
prices 1319 China-clay industry, annual review 1318	nearing, new method 955
Chlorine, uses 1318	number 965
Chrome ore, export premium, allowance by	type965
Office of Price Administration 633	yield         967, 975           Coke-oven gas, production         994, 996, 997           sales         997
Chromite, beach sands as source, mineral dress-	Coke-oven gas, production 994, 996, 997
ing, Bureau of Mines study637	Volue 997
Conglimation	Value 997 Coke retorts, number 993
monthly surveys, Bureau of Mines 638 deposits, Bureau of Mines and Geological	Colemanite, sales 1567 Colombia, bauxite, deposit 708
deposits, Bureau of Mines and Geological	Colemanite, sales 1507 Colombia, bauxite, deposit 708
ourvey investigations 63/	gold, data
foreign trade 639	gold, data 119, 125 platinum metals, data 808, 810 Colorado, Adams County, metals, production 320
German-Turkish agreements 643	Colorado, Adams County, metals, production 300
grade specifications 633	321, 327, 329
Metals Reserve Co. contracts	321, 327, 329 bituminous-coal industry, data. 837, 852, 853, 856, 858, 863, 864, 869, 870, 876, 881, 882, 883, 886, 890 Boulder County, metals, production. 320, 321,
prices 633	858, 863, 864, 869, 870, 876, 881, 882, 883, 886, 8 90
production634	Boulder County, metals, production 320, 321.
purchases, Metals Reserve Co	
salient statistics 631 stock-pile purchases 632	Chaffee County, metals, production 320, 321.
Stock-pue purchases	324 325 326 327 330
Chromite industry approximately 638	Clear Creek County, metals, production 320.
Chromite industry, annual review 631	321, 324, 325, 326, 327, 330
Chromite ores, price control 633 Chromium alloys, delivery, control, War Production Board 632	copper, production 135, 136, 137,
Production Roard con	138, 139, 318, 319, 320, 322, 323, 324, 325, 326, 327
Chromium metal, delivery, control, War	Costilla County, metals, production 320, 327
Production Board 632	Cripple Creek district, metals, production 342
Chrysotile asbestos. See Asbestos.	Custer County, metals, production 320,
Clay, as source of alumina 1200 l	321, 326, 327, 331
consumption 1315 miscellaneous, annual review 1326	Dolores County, metals, production 320,
miscellaneous, annual review 1326	321, 324, 325, 327, 331 Eagle County, metals, production 320,
sales1318, 1327	Eagle County, metals, production 320, 321, 324, 325, 326, 327, 332
salient statistics 1316, 1317	El Paso County, metals, production 332
technologic developments1328	fluorspar industry 1200 1400
Clay industries, annual review 1315	fluorspar industry 1399, 1400 Fremont County, metals, production 320,
Clay products, production 1327 Clay tile, data 1328	321 324 325 327 333
Clay tile, data1328	Garfield County, metals, production 320
Coal. coking. stocks oso i	321, 324, 325, 327, 333  Garfield County, metals, production 320,  Gilpin County, metals, production 321, 326, 327
culm-bank, put through breakers 937  See Anthracite; Bituminous coal; Fuel briquets; Lignite; Packaged fuel; Peat.  Coal-gas industry, salient statistics 992  Coarle Bitin Mid-try Will-	320.
See Anthracite; Bituminous coal; Fuel	321, 324, 325, 326, 327, 333
Cool-reg industry, colient statistics	gold, production
Coastal Plain, Midway-Wilcox contact, baux-	97, 98, 99, 101, 102, 103, 109, 111, 115, 116, 117,
ite denosite	97, 98, 99, 101, 102, 103, 109, 111, 115, 116, 117, 318, 319, 320, 321, 322, 323, 324, 325, 326, 327
ite deposits 689	gold dredges, list 105
Cobalt, consumption 651 deposits, Bureau of Mines exploration 652 foreign trade	
foreign trade 653	Golden Cycle mill, metals, production 332
metallurgical tests, Bureau of Mines 652	Grand County, metals, production 320,
production 651	321, 326, 327, 333
11868 651	Gunnison County, metals, production 320, 321, 322, 322
Cobalt industry, annual review 651	321, 324, 325, 326, 327, 334 Hinsdale County, metals, production 320,
Jodait-nickel concentrates, Bureau of Mines	320, 321, 324, 325, 326, 327, 334
investigations 646	iron ore, consumption 581
Coke, beehive, distribution	Jefferson County, metals, production, 320, 327, 324
price control	Lake County, metals, production 290
production 951,	Lake County, metals, production 320, 321, 324, 325, 326, 328, 334
955, 957, 958, 959, 960, 961, 963, 964, 980	La Plata County, metals, production 320,
byproduct, distribution 984	321, 326, 328, 336
price control 953	Larimer County, metals, production 320,
production 951,	321, 324, 328
955, 957, 958, 959, 960, 962, 963, 964, 979	lead, production
consumption 921, 977, 986, 987	170, 318, 319, 320, 322, 323, 324, 325, 326, 327
foreign trade 991 foundry, production 978	Leadville district, metals, production 334

	Page
Colorado, Mesa County, metals, production. 320,	Copper, secondary, analysis 528
321, 326	annual review 526
metals, production, annual review 317	consumption 529
metallurgic industry, review 323 minerals, production 43, 45, 48, 52	imports531
Mineral County, metals, production 320,	prices 539 price control 530
321, 324, 325, 326, 328, 336	priority control133
mining industry, review 321	products, production 528
molybdenum, review 659	recovery 141, 521, 526
molybdenum mine, purchase, by Defense	stocks529
Plant Corporation 661	shipping facilities 128
Montezuma County, metals, production 320, 321, 324, 325, 326, 328, 336	statistics, release forbidden, by Office of War
Montrose County, metals, production 320,	Information 130 stocks 142
321, 326, 328, 336	Government purchase 128
natural gas, review1131,	Copper-base alloys, priority controls 133
1132, 1133, 1134, 1136, 1150, 1151, 1152, 1154, 1157	Copper-base alloys, priority controls 133 Copper Branch, War Production Board, organization 130
ore, classification 322	organization 130
Ouray County, metals, production 320,	statement, on copper requirements 129
321, 324, 325, 326, 328, 336	Copper chemicals, allocation control
Park County, metals, production 320.	Copper industry, annual review 127 labor conditions 132
321, 324, 325, 326, 328, 337	world aspects 151
petroleum industry, data1036, 1037, 1041, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1106	world aspects         151           Copper mines, accidents         1544           men employed         9, 1540, 1544
Pitkin County, metals, production 320,	men employed
321, 324, 325, 326, 328, 339	Copper ores, recoverable content 137
pyrites, data 1359	Copper Recovery Corporation, stocks, sale 128
pyrites, data 1359 Rio Grande County, metals, production 320,	Copper scrap. See Copper, secondary.
321, 324, 325, 328, 339	Copper sulfate, allocation control 141
Routt County, metals, production 320,	Cornwall stone, imports 1421
321, 324, 325, 328, 339 Saguache County, metals, production 320.	141   Cornwall stone, imports   142    Corundum, foreign trade   1347, 1348     review   1342    Costa Rica, gold, data   119, 124    Critical minerals, stock pile, list   21     See give these minerals   111, 124    21   22   23   24     24   25   26   26   26     25   26   26   26     26   26   26     27   27     28   28   28     29   28     20   28     20   28     21     22     23     24     25     26     26     26     27     28     29     20     20     20     20     20     21     22     23     24     25     26     26     26     27     27     28     29     20     2
Saguache County, metals, production 320, 321, 324, 325, 326, 328, 339	review1342
San Juan County, metals, production 320,	Costa Rica, gold, data119, 124
321, 324, 325, 326, 328, 340	Critical minerals, stock pile, list 21
San Miguel County, metals, production 320,	occ disc these minerals in this index.
321, 324, 325, 326, 328, 341	Crocidolite, uses 1424 Cryolite, allocation control 1411
silver, production 85,	artificial, manufacture
97, 98, 99, 101, 102, 103, 111, 113, 115, 117, 318,	artificial, manufacture 1411 imports 1411
319, 320, 321, 322, 323, 324, 325, 326, 327	Metals Reserve Co. contracts 27
silver mines, list 94	source1410
Summit County, metals, production 320,	uses1410
321, 324, 325, 326, 328, 341 Teller County, metals, production 320,	Cuba, antimony, deposits 793
Teller County, metals, production	barite, data
thallium, recovery, as zinc-cadmium refinery	iron ore, production582
byproduct829	magnesite, data1497
tungsten, review 676, 678 vanadium ore, deposits 666	manganese ore, data629
vanadium ore, deposits 666	pickel, data650
zine, production 189,	facilities, establishment by Defense Plant
318, 319, 320, 322, 323, 324, 325, 326, 327	Cupola furnaces, ferrous scrap and pig iron,
Columbite, foreign trade 823, 824 prices 824	consumption 552 558
Columbium, annual review 823	
	Cyanamid, allocation control 1524
uses 824	consumption 552, 558 Cyanamid, allocation control 1524 imports 1524
uses824	imports 1524 Cyprus, asbestos industry, status 1434
uses 824 Columbium metal, prices 824	imports 1524
uses       824         Columbium metal, prices       824         Columbium ores, import control       823	imports
uses       824         Columbium metal, prices       824         Columbium ores, import control       823         Concrete, sales       1238, 1239	imports 1524 Cyprus, asbestos industry, status 1434
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53	imports. 1524 Cyprus, asbestos industry, status. 1434 pyrites, data. 1361, 1362
uses       824         Columbium metal, prices       824         Columbium ores, import control       823         Concrete, sales       1238, 1239	imports. 1524 Cyprus, asbestos industry, status. 1434 pyrites, data. 1361, 1362  D  Defense Plant Corporation, construction, tin smelter. 28
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders.         See War Production	1524   Cyprus, asbestos industry, status.   1434   Cyprus, asbestos industry, status.   1361, 1362   D
uses       824         Columbium metal, prices       824         Columbium ores, import control       823         Concrete, sales       1238, 1239         Connecticut, minerals, production       43, 48, 53         Conservation orders. See War Production         Board.	Imports.   1524   Cyprus, asbestos industry, status.   1361, 1362   D
uses 824 Columbium metal, prices 824 Columbium ores, import control 823 Concrete, sales 1238, 1239 Connecticut, minerals, production 43, 48, 53 Conservation orders. See War Production Board. Construction contracts, record value 1194 Controls. See War Production Board.	imports
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Conservation orders         43, 48, 53           Conservation orders         See War Production           Board         1194           Controls         See War Production Board           Controlled Materials Plan, features         5, 133, 705	imports.   1524   Cyprus, asbestos industry, status.   1434   pyrites, data.   1361, 1362   D
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         Board.           Construction contracts, record value         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714	1524   Cyprus, asbestos industry, status
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         Board.           Construction contracts, record value         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Construction contracts, record value         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological	Imports.
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Contruction contracts, record value         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         320 years           Survey investigations         130, 131	Imports.
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Construction contracts, record value         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         Survey investigations         130, 131           foreign trade         145	Imports
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Construction contracts, record value         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         13           deposits, Bureau of Mines and Geological         Survey investigations         130, 131           foreign trade         145           restriction         128	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Controls. See War Production Board.         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         Survey investigations           Survey investigations         130, 131           foreign trade         145           restriction         128           limitation orders         128	Imports
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         23, 48, 53           Conservation orders. See War Production         1194           Construction contracts, record value         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         Survey investigations         130, 131           foreign trade         145           restriction         128           limitation orders         128           Metals Reserve Co. contracts         27	Imports.
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Controlles. See War Production Board.         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         132           Survey investigations         130, 131           foreign trade         145           restriction         128           Imitation orders         128           Metals Reserve Co. contracts         27           overproduction, Metals Reserve Co. bonus	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Construction contracts, record value         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         Survey investigations         130, 131           foreign trade         145           restriction         128           Imitation orders         128           Metals Reserve Co. contracts         27           overproduction, Metals Reserve Co. bonus         131           payment         131           prices         48, 143	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Controls. See War Production Board.         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         131           Survey investigations         130, 131           foreign trade         145           restriction         128           Imitation orders         128           Metals Reserve Co. contracts         27           overproduction, Metals Reserve Co. bonus         payment         131           prices         48, 143           price control         132, 134	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Construction contracts, record value         1194           Controlles. See War Production Board.         5, 133, 705           Conservation Order, mercury         714           Controlled Materials Plan, features         5, 133, 705           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         Survey investigations         130, 131           foreign trade         145           restriction         128           limitation orders         128           Metals Reserve Co. contracts         27           overproduction, Metals Reserve Co. bonus         131           payment         131           primary, production, mine         135	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Controlled Controls. See War Production Board.         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         135           Survey investigations         130, 131           foreign trade         145           restriction         128           limitation orders         128           imitation orders         27           overproduction, Metals Reserve Co. bonus         27           payment         131           prices         48, 143           prices         48, 143           prices         48, 143           primary, production, mine         135           refinery         139	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Controlled Controls. See War Production Board.         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         135           Survey investigations         130, 131           foreign trade         145           restriction         128           limitation orders         128           imitation orders         27           overproduction, Metals Reserve Co. bonus         27           payment         131           prices         48, 143           prices         48, 143           prices         48, 143           primary, production, mine         135           refinery         139	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Construction contracts, record value         1194           Controlls. See War Production Board.         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan, features         5, 133, 705           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         Survey investigations           Survey investigations         130, 131           foreign trade         145           restriction         128           Metals Reserve Co. contracts         27           overproduction, Metals Reserve Co. bonus         131           prices         48, 143           prices         48, 143           prices         48, 143           price control         132, 134           primary, production, mine         135           refinery </td <td>  Imports.   1524    </td>	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Construction contracts, record value         1194           Controlls. See War Production Board.         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan, features         5, 133, 705           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         Survey investigations           Survey investigations         130, 131           foreign trade         145           restriction         128           Metals Reserve Co. contracts         27           overproduction, Metals Reserve Co. bonus         131           prices         48, 143           prices         48, 143           prices         48, 143           price control         132, 134           primary, production, mine         135           refinery </td <td>  Imports.   1524    </td>	Imports.   1524
uses         824           Columbium metal, prices         824           Columbium ores, import control         823           Concrete, sales         1238, 1239           Connecticut, minerals, production         43, 48, 53           Conservation orders. See War Production         1194           Construction contracts, record value         1194           Controlled Materials Plan, features         5, 133, 705           Conservation Order, mercury         714           Copper, consumption         141           Controlled Materials Plan         133           deposits, Bureau of Mines and Geological         Survey investigations         130, 131           focign trade         145           restriction         128           limitation orders         128           Metals Reserve Co. contracts         27           overproduction, Metals Reserve Co. bonus         13           prices         48, 143           price control         132, 134           primary, production, mine         135           refinery         139           smelter         134           priority control         133           smelter         134           priority control         133 <td>  Imports.   1524    </td>	Imports.   1524

Page	Pag
Diamond, market	Feldspar, imports     142       production     1413, 1414, 142       sales     1413, 1414, 1415, 141
production1516	production1413, 1414, 142
share dealings 1515	sales1413, 1414, 1415, 141
stocks 1515 Diamond industry, annual review 1515	salient statistics 141: technologic developments 1419
Distante prices 1333	uses1410
review1332	Feldspar industry, annual review 141
sales 1331, 1332	Ferro-alloys, foreign trade 570, 600
11SeS 1333	production, consumption of ferrous scrap
Dimension stone, annual review 1224 sales 1222, 1223, 1224	and pig iron 56
Sales	sament statistics
use, trends	production 570, 603 shipments 570, 603
Doerner process, for producing magnesium by	Ferro-alloy blast furnances, number 59
electrothermic reduction 776	Ferro-alloys industry, annual review 603
Dolomite, as source of magnesium, investi-	Ferroboron, production 604, 606
gations 771, 776, 1248	uses606
extraction of magnesium from, by ferrosilicon	Ferrocerium, uses 82
process776 recovery of magnesia from, methods1498	Ferrochromium, consumption 60
sales 1498	delivery, control, War Production Board 633 foreign trade
Dow process, magnesium, description 769	foreign trade 600 Ferrocolumbium, allocation control 823
Drilling orders, natural-gas wells 1129	prices 824
Dumortierite, production 1529	production 82
###[### 이 10 10 10 10 14 15 16 16 16 16 16 16 16 16 16 16 16 16 16	uses
. The second of the ${f E}$	Ferromanganese, consumption 622
Factorn States conner production 125 126	foreign trade 570, 606, 607, 614, 624, 624
Eastern States, copper, production	manufacture, manganese ore consumed 626, 626
gold, production 85, 97, 98, 101, 102,	l producers list 629
103, 109, 111, 115, 116, 117, 350, 351, 353, 354, 355	production 604
lead, production	production 604 shipments 570, 604
metals, production, annual review349	stocks 622
metallurgic industry, review 354 mining industry, review 353	Ferromolybdenum, production 604
ore classification 354	Ferrosilican foreign trade
silver, production 85, 97, 98, 101, 102,	production 604 605
103, 109, 111, 115, 116, 117, 350, 351, 353, 354, 355	FerromayBuenum, production
zine, production 189, 350, 352, 353, 354	Ferrosilicon process, for extracting magnesium
ore, classification 85, 97, 98, 101, 102, 103, 109, 111, 115, 116, 117, 350, 351, 353, 354, 355 zinc, production 189, 350, 352, 353, 354 Economic Defense Board, functions, orders	
, deming	Ferrotitanium, manufacture 606
Economic Stabilization, Office of, functions. 11, 12 Economic Warfare, Board of, export control,	uses 600 Ferrotungsten, production 604, 605
molybdenum 658	value 605
molybdenum 658 functions, orders defining 10, 16, 30	value 605 Ferrovanadium, production 604
investigation, sillimanite deposit	value 606
organization 16	value 600 Ferrous scrap, annual review 543
stock-pile purchases, copper 128	consumption 543, 544, 550
minerals, foreign 21 transfer of authority from Reconstruction	in ferro-alloys 562 prices 545
Finance Corporation to30	prices 545 price control 545
Ecuador, copper, data 153, 158	l salient statistics - 544
gold, data	stocks. 544, 546 Fertilizers, production, Tennessee Valley Authority. 1371 Finland, copper, data. 153, 158
realgar, deposit 761 silver, data 121, 125	Fertilizers, production, Tennessee Valley
Eire, barite, data 1439	Authority 1371
pyrites, data 1362	nickel, data 650
Electric plants, fuel efficiency 838	Fire clay, exports1322
Electric steel, manufacture 609	prices 1323
Emergency Management, Office for, functions11	sales 1317, 1322
Emery, foreign trade       1347, 1348         review       1342         sales       1331, 1342         Employment       1120         Figure 1       1120         1120       1120	salient statistics 1316
1942 galeg 1941	shipments 1322
Employment, mineral industries 7, 1539	war uses 1321
Ensom salts, foreign trade 1501	Fire-clay industry, annual review 1321
Essential minerals, stock pile, list21  See also these minerals in this index.	Flint, foreign trade 1347, 1348
See also these minerals in this index.	Flint pebbles, production 1339
Europe. See Bulgaria; Eire; Finland; France;	Florida, minerals, production 43, 45, 48, 54
Germany; Great Britain; Greece; Hungary; Ireland, Northern; Italy; Norway; Portugal; Spain; Sweden; Switzerland; Turkey; Union of Socialist Soviet Republics; United Kingdow; Yurselytie	phosphate rock, review 1364, 1369 titanium ores, data 812
Norway: Portugal: Spain: Sweden:	zircon, production, as accessory of rutile and
Switzerland; Turkey; Union of So-	ilmenite 829
cialist Soviet Republics; United King-	Fluorspar, consumption 1397
uom, rugosiavia.	Fluorspar, consumption 1397 duty, reduction, trade agreement with Mex-
Exports, Office of, functions 31	100 1393, 1408
Export control, molybdenum 658	foreign trade 1392, 1407
Export premium, Office of Price Administra-	monthly survey, Bureau of Mines1391 price control1393, 1398
tion, chrome ore 633	production 1393
· ·	salient statistics 1392
${f F}$	shipments
Toollity Clearance Deardt-11-1	by uses 1395
Facility Clearance Board, establishment	supervision, by War Production Board 1392 specifications 1396
Facility Review Committee, establishment 1196 Federal Reserve Board, construction indexes 1194	specifications 1396 stocks 1392 1397 1399
Feldspar, consumption 1416	stocks1392, 1397, 1399 technologic developments1399
extinguishing incendiary bombs with 1419	uses1395
fluxing properties 1419	uses1395 Fluorspar industry, annual review1391

Page	Page
Fluorspar plants, Army Air Forces, protection_ 1393	Georgia, manganese ore, data 616, 617, 618
new, list1399	Metals, production, annual review   355   minerals, production   43, 45, 48, 55   silver, production   85, 97, 101, 353, 355   Germanium, deposits   825   Germanium metal, prices   825   Germany, aluminum, production   706, 708   barite data   1430, 1440
Foundry coke. See Coke. France, aluminum, review	minerals, production 43, 45, 48, 55
magnesium, data 778, 779	Germanium denosite
French Cameroun, rutile, data 817,818	Germanium metal, prices 825
French chalk, foreign trade 1387, 1388, 1389	Germany, aluminum, production 706, 708
French Morocco, cobalt, data 654	barite, data
manganese ore, production 629	bauxite, foreign trade708
molybdenum, review	chromite, agreement with Turkey 643
Fuels, supplies 922 Fuel briquets, binders 1012	copper, review 153, 158
consumption 921	ferrous scrap, review 564, 566 industrial diamonds, shortage 1518
consumption   921   distribution   1013   foreign trade   1007, 1014   plants, number   1007, 1010   size   1011   prices   1009, 1000   1009, 1009	magnesite, data 1497 magnesium, data 778, 779
foreign trade1007, 1014	magnesium, data 778, 779
plants, number 1007, 1010	sulfur, data       1358         tin, review       746, 747, 751         vanadium, review       670
nrices 1000 1010	vanadium review
	Gilsonite, prices 1185
raw fuels 1011 salient statistics 1007	1 Sales 1185
salient statistics	Glass manufacture, antimony, arsenic, and
shape 1013	cerium as reagents 758
value1007, 1009	Glauber's salt, prices 1507 sales 1505
weight 1013 Fuel briquets industry, annual review 1003	sales1505 Gold, consumption88
Fuel oil, consumption 921	foreign trade 89
Fuel oil, consumption 921 demand 1030, 1072, 1101, 1109, 1110 foreign trade 1072, 1102, 1105, 1108, 1109, 1110	Government regulations 80
loreign trade 1072, 1102, 1105, 1108, 1109, 1110	nrices 49.96
prices 1112 production 1072, 1102, 1107, 1109, 1110	production, dredges 103
rationing 1084 1101	mill 103 mine 91, 96, 101
sales 922, 1103, 1104, 1106	mint report 92
rationing 1084, 1101 sales 922, 1103, 1104, 1106 stocks 1072, 1102, 1108, 1109, 1110, 1111	placer103
yields       1109, 1110         Fuller's earth, competition       1323, 1324	refinery 85
foreign trade 1325	salient statistics 80
prices1325	stocks 87 supply, domestic 91
sales	uses 88
salient statistics	Gold Coast, bauxite, review 705, 708
Fuller's earth industry, annual review 1324	manganese ore, data 629 Gold dredges, list 104
Furnace coke. See Coke.	Gold dredges, list 104 Gold industry, annual review 79
G	Gold industry, annual review 79 labor data 107
Garnet, abrasive, prices 1342	world aspects 118
review 1341	Gold mines, accidents 1544
sales1331, 1341 Gas, manufactured, sales922	leading, list 93 men employed 107, 1540, 1544
Gas, manufactured, sales 922 Gas-house coke. See Coke.	number 95
Gasoline, aviation, production program 1092	War Production Board limitation order 80
consumption 1095	Gold Mine Closing Order
consumption 1095 demand 1030, 1072, 1085, 1087	Gold ore, production 98
10reign trade 10/2, 1085, 1087	Granite, crushed, sales 1242
prices 1090 production 1072, 1077, 1079, 1085, 1086, 1088	foreign trade 1254 sales 1222, 1224, 1226,
rationing 1084, 1085	Granite quarries, accidents 1546
shipments 1096 stocks 1072, 1076, 1085, 1092, 1094	men employed 1540, 1546
stocks	Graphite, annual review 1525
yields 1090 Gem stones, foreign trade 1513	domestic, sources, Bureau of Mines investigations 1527
production1510	gations 1527
Gem-stone industry, annual review 1509	foreign trade
Gem-stone trade, effects of war 1514	import control 1525
Geological Survey, investigations, magnesium	Metals Reserve Co. contracts 27
well, as source of potash salts 1455 strategic minerals, bauxite, deposits 689	prices 1527 production 1527
peryllium ore, deposit	production 1527 Graphite plants, Reconstruction Finance Cor-
chromite637	poration, loans 1527
copper131	Gravel, foreign trade 1279
magnesium 1500	preparation, degree 1274
mercury, deposits 714 molybdenum, deposits 661	prices 1278 price control 1278 price control 1278 sales 1266, 1267, 1271, 1273 transportation, method 1274 (Frevel industry entrol 1274
nickel, deposits646	sales 1266, 1967, 1971, 1973
phosphate rock, deposits, as source of	transportation, method 1274
vanadium 668	Gravel industry, annual review 1265
tin 735 tungsten 675	Government-and-contractor operations 1265,
organization 20	men employed 1266, 1267, 1268, 1278
war activities 20.32	principal trends 1276, 1278
war activities 20, 32 Georgia, asbestos, production 1426	1265   Government-and-contractor operations   1265   1266, 1267, 1268, 1273   1266, 1267, 1268, 1273   1266, 1267, 1268, 1273   1276, 1278   1275
barite, data	Great Britain, sulfur, data 1358
Bureau of Mines investigations 689	Green bill to remove restrictions on sil-
production 688	Green bill, to remove restrictions on silver83 Greenland, cryolite, review1410
hituminous-coal industry data 6837	Grinding pebbles, review 1239
	sales 1331, 1338
gold, production 85, 97, 101, 351, 353, 355	Grinding pebbles, review 1338 sales 1331, 1338 Grindstones, foreign trade 1347, 1348 review 1336, 1337 sales 1331, 1336, 1337
iron ore, data	review1336
1520	Sauco

Pag	
Gross-Almerode clay, imports 1316	
Gypsum, calcined, processing plants, equip-	368, 370, 371, 372, 373, 375, 38
ment 128' 1287 1289 1200	Lewis County, metals, production 367, 368, 37
production1284, 1287, 1288, 1294 crude, production1284, 1287, 1294	mercury, data
foreign trade 199	metals, production, annual review 36
price control	metallurgic industry, review 36
sales, distribution 128	
salient statistics 128	mining industry, review 36
substitution for sulfur, at nickel smelter 129	
supplies, critical state     128       uses     128       Gypsum board, demand     128       sales     1290, 1291, 129	ore classification 369 Owyhee County, metals, production 367
Gypsum board, demand 128	368, 370, 371, 372, 373, 375, 38
sales 1290, 1291, 129	phosphate rock, as source of vanadium 667, 66
Gypsum cement, on-wen use 129	5   sales 1364, 1373, 1374, 137
Gypsum industry, annual review 128	
developments 129 Justice Department suit 128	
labor shortage 128	
Wages 128	98 99 101 102 103 109 111 113 115 116 117
Gypsum plaster, uses 129 Gypsum products, foreign trade 129	364, 365, 367, 368, 369, 370, 371, 372, 373, 374.
Gypsum products, foreign trade129	tungsten, review 676, 67
prices 129, sales 1284, 1289, 129 Gypsum tile, sales 1290, 1291, 129	Twin Falls County, metals, production, 367
Gynsum tile sales 1200, 1201, 1209, 1201	368, 376 Valley County, metals, production 367
3 pour 100, baron 1201, 120	368, 370, 371, 372, 373, 376, 38
is the figure $\mathbf{H}$ , the set $\mathbf{H}$ is the $\mathbf{H}$	Washington County, metals, production 367
	368, 373, 37
Hansgirg process, magnesium, description 771	zinc. production 189
Heliarc welding, magnesium 77	_
Helvite deposit	Illinois, bituminous-coal industry, data 837,
Helvite, deposit	852, 853, 856, 858, 863, 864, 869, 870, 871, 875 876, 880, 881, 882, 883, 886, 891.
gold, data119, 12	fluorspar industry 1399, 140
_silver, data 121, 12	lead, production 169, 170, 297, 29
Hones. See Oilstones.	metals production annual review 29
suver, data 121, 12 Hones. See Oilstones. Hungary, bauxite, review 705, 70 magnesium, data 77	minerals, production 43, 45, 48, 5
magnipham, wasa	minerals, production 43, 45, 48, 5 natural gas, review 1131, 1132, 1133, 1134, 1136, 1150, 1151, 1152, 1154, 1156, 1157
	petroleum industry, data 1036
	1037, 1038, 1039, 1041, 1060, 1064, 1065, 1068
Idaho, Ada County, metals, production 367 368, 370, 372, 374, 37	petroleum indústry, data 1036 1037, 1038, 1039, 1041, 1060, 1064, 1065, 1068 1070, 1071, 1095, 1096, 1100, 1106.
Adams County, metals, production 367	'   Dyrites, data 135
260 272 274 27	Silver, production
antimony, data	zine production 186, 189, 297, 298, 29
Benewah County, metals, production 367	zinc production 186, 189, 297, 298, 29 Ilmenite, consumption 81
368, 37 bituminous-coal industry, data	
858, 863, 864, 869, 88	inventory restrictions, removal, by War Production Board 81
Diatie Country, metals, production	h maiona 91
368, 371,372, 373, 374, 37	production 812.81
Boise County, metals, production 367,	production 812, 81 stocks 81-
368, 370, 372, 373, 374, 37 Bonner County, metals, production 367	Ilmenite tailings, recovery of vanadium from,
368, 371, 372, 373, 374, 37	Bureau of Mines study 810
Bonneville County, metals, production 367	imports, Office of, functions
260 27	
Boundary County, metals, production 367, 368, 371, 372, 374, 37	niobium ores 82
Butte County, metals, production 367,	quartz crystals 153
368, 371, 372, 374, 37	rutile
Camas County, metals, production 367	scrap metals
368, 371,372, 373, 37	
Clearwater County, metals, production 368, 374, 37	-in-anisam concentrates
cobalt, deposits, Bureau of Mines explora-	Import licenses, antimony ore 78
tion65	India. See British India.
Coeur d'Alene region, metals, production 38	Indiana, bituminous-coal industry, data 837
copper, production 135, 136, 137, 138,	852, 853, 856, 858, 863, 864, 869, 870, 871, 875, 876, 880, 881, 882, 883, 886, 892.
139, 364, 366, 367, 370, 371, 372, 373, 374	limestone sales 123:
Custer County, metals, production 367, 368, 370, 371, 372, 373, 374, 378	limestone, sales 123 minerals, production 43, 45, 48, 5
Elmore County, metals, production 367.	natural gas, data
368, 370, 371, 372, 373, 375, 37	1133, 1134, 1137, 1150, 1152, 1154, 1156, 115
Gem County, metals, production 367, 377	petroleum industry, data 1036, 1037, 1043, 1060 1064, 1065, 1068, 1071, 1095, 1096, 1100, 110
368, 371, 372, 373, 375, 376	nyrites, data
gold, production 85, 97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116, 117, 264, 265, 267, 269, 260, 270, 271, 272, 273, 274, 274, 274, 274, 274, 274, 274, 274	
304, 300, 301, 300, 303, 310, 311, 312, 313, 311	Indium, annual review 82 use, to prevent corrosion 82
gold deadges 10	I Indium metal, brices
Idaho County, metals, production., 367. 368, 370, 371, 372, 373, 375, 38	production82 Insecticides, arsenic compounds as, use75
568, 570, 571, 572, 573, 575, 58	
Jerome County, metals, production 367, 368, 37 Latah County, metals, production 367, 368, 37	of war activities, foreign
368, 375, 38	I Interior, United States Department of, war
lead, production 169	work, foreign
170, 364, 366, 367, 370, 371, 372, 373, 37	Inventories, control

	na a sa a sa a sa a sa a sa a sa a sa a
Page	Page Venges lend production 160 170 207 208 200
Iodine, annual review	Kansas, lead, production 169, 170, 297, 298, 300 metals, production, annual review 300
imports 1504 prices 1504	minerals, production 43, 45, 48, 58
	natural gas, review 1131.
Iowa, bituminous-coal industry, data	1132, 1133, 1134, 1138, 1150, 1151, 1152, 1154, 1157
	petroleum industry, data 1036, 1037, 1038, 1039, 1043, 1060, 1064, 1065, 1068,
minerals, production 43, 48, 57	1070, 1071, 1095, 1096, 1100, 1106.
minerals, production	zinc, production 189, 297, 298, 300
price 804	Kaolin, exports. 1320 sales. 1316, 1317, 1319 salient statistics. 1316
refined, recovery803, 804	salient statistics 1316
secondary, recovery	
stocks         807           Iron ore, beneficiation         578	Keene's cement, sales
plants, men employed 595	852, 853, 856, 858, 863, 864, 869, 870, 872, 875, 876,
consumption 580	880, 881, 882, 883, 886, 893.
foreign trade 570, 582 manganiferous, consumption 627	Huorspar industry 1899, 1403
snipments	metals, production, annual review
Metals Reserve Co. contracts 27	minerals, production 43, 45, 48, 58
prices584 production569, 570, 571, 573, 596	880, 881, 882, 883, 886, 893. fluorspar industry
	petroleum industry, data 1036, 1037, 1044, 1060,
Solient statistics	1064, 1065, 1068, 1070, 1071, 1095, 1096, 1100, 1106
shipments 570, 573, 576	
tenor595	Kernite, sales
value 579	foreign trade 1072, 1099
Iron-ore industry, annual review 573	prices 1101 production 1072, 1098
men employed 592, 595, 1540, 1544	production 1072, 1098
Iron-ore mines, accidents     1544       men employed     592, 595, 1540, 1544       output per man     592, 595	sales     1100       stocks     1072, 1098, 1099       yields     1074, 1075
principal, list 576 Iron oxide pigments, domestic manufacture 1531	yields1074, 1075
manufactured foreign trade 1532	Kieserite, calcined, foreign trade 1501 Kyanite, annual review 1528
prices 1532	foreign trade 1528, 1529
review 1531	nrices 1529
Iron products, foreign trade 610	price control 1529 production 1528, 1529
prices 1532 review 1531 sales 1531, 1532 Iron products, foreign trade 610 Iron scrap, consumption 544, 550 in ferro-alloys 562	salient statistics 1528
foreign trade	kan tanàn ang atau ang atau at ang atau at ang at at at at at at at at at at at at at
inventories, increase, permission	${f L}$
price control	Lake Superior district, iron-ore mining,
stooks 544, 546	review 583  Land pebble, foreign trade 1376
tariff energian legislation 546	prices1368
Iron scrap industry, annual review	sales 1364
barite, data1439, 1440	Land plaster, uses 1289 Lead, antimonial, foreign trade 175
mercury, data	production166, 167, 782, 786
Iron sorap industry, annual review   543   Italy, aluminum, data   706, 710   barite, data   1439, 1440   mercury, data   727, 728   sulfur, data   1358   tin, data   746, 747, 752	conservation, measures164
	Lead, antimonial, loreign trade. 170 production. 166, 167, 782, 786 conservation, measures. 164, 171 debismuthizing, magnesium for, use production between the state of the servation of the servation for the ser
Jade, deposits1519	
production 1511	foreign trade 163, 164, 173 Metals Reserve Co. contracts 27, 164
Jamaica, bauxite, review 710	overproduction, bonuses 165
antimony, data 793	pig, foreign trade174, 176
bauxite, reserves 710	overproduction, bonuses
ferrous scrap, data564, 566	refinery164, 166
Jade, deposits	refinery. 164, 166 sources 166
zinc, data 199, 200, 202	
Jewels, instrument and chronometer, creation of domestic industry	1011   1011
imports1520	consumption535
Jewelry, fashions	foreign trade 536
price ceilings 1513 sales, increase 1509	price control535
Tewelry industry, annual review 1509	products, production 534 recovery 164, 167, 533
	recovery164, 167, 533
Government regulations 1514	stocks 535 stocks 164, 170
Johore, bauxite, data 705. 712	stock pile103
Government regulations 1514 Jewelry trade, metal shortage 1513 Johore, bauxite, data 705, 712 Justice Department, suits, Aluminum Co. of	supply
America	use, as insecticide
sulfuric-acid manufacturers, postponement	Tead industry, annual review 163
of trial	world aspects 176 Lead mines, accidents 1544
. <b>K</b>	men employed1544
<del>-7</del> →	Tood nigments consumption 210
Kansas, bituminous-coal industry, data 837, 852, 853, 856, 858, 863, 864, 869, 870, 872, 875, 883,	foreign trade 207, 217 manufacture, raw materials 207, 217
852, 853, 856, 858, 863, 864, 869, 870, 872, 875, 883, 886, 893.	prices207, 216
200, 000	

Page	Page
Lead, production	Louisiana, magnesium plant 770
salient statistics 207	minerals, production 43, 46, 48, 59 natural gas, review 1128, 1131, 1132,
Lead pigments industry, annual review 205	
Lead salts, foreign trade 217 Lead scrap. See Lead, secondary	natural gasonne, data
Lead scrap. See Lead, secondary. Lead sulfate, basic, consumption 210	petroleum industry, data
sales 208, 209 Lead-zinc mines, employment 9	1037, 1038, 1039, 1045, 1060, 1064, 1065, 1068
Liberia, bauxite, deposits 711	
Light oil, production 956, 992, 995, 996, 1001 Lignite, cleaning, mechanical 883	sulfur, production       1351, 1352         Lubricants, consumption       1114, 1116         demand       1030, 1072, 1115         foreign trade       1080
Lignite, cleaning, mechanical 883	demand 1030, 1072, 1115
distribution 832 loaded for shipment 864	
production 835, 836, 850, 852, 855, 856, 904, 905, 992	production 1116
salient statistics 835	1079 1115
	yield1115
value, average       860         Lignite industry, annual review       831, 904         trends       847, 848, 850         Lignite mines, loading, mechanical       870         mechanization, data       870         men employed       832, 835, 848, 850, 853         mining methods       869, 906         number       858, 906         power drilling       876         size       878	M
trends847, 848, 850	Madagascar, mica, data 1472, 1473, 1474, 1476
mechanization data 877	
men employed 832, 835, 848, 850, 853	Magnesia, foreign trade
mining methods869, 906	Drices 1404
number 858, 906	1 recovery from dolomite, methods 1400
size858	refractory, sources 1497 Magnesite, deposits, as source of magnesium.
strikes, suspensions, and lock-outs849, 864	investigation 776
stripping operations 871, 906	prices 1492, 1494 price control 1494
stripping operations     871, 906       working day     862       Lime, agricultural, sales     1298, 1299, 1302, 1303, 1304       building, sales     1298, 1299, 1300, 1303, 1304, 1305       captive tonnage     1301       chemical, demand     1298       sales     1298, 1299, 1303, 1304, 1305       consumption     1307       foreign trade     1313	price control 1494 production of magnesium oxide from,
building, sales 1298, 1299, 1300, 1303, 1304, 1305	I INVESTIGATION 77e
captive tonnage 1301	Salient Statistics
sales 1298, 1299, 1303, 1304, 1305	
consumption	Magnesium, arc welding, with helium 7777 consumption 768, 773
1010	corrosion characteristics
	distribution, preference order 775
saies       1298, 1300, 1303, 1303, 1306, 1306, 1307         supplies       1308, 1309, 1310         industrial, sales       1298, 1299, 1303, 1304, 1305         metallurgical, demand       1299         prices       1291	extraction from dolomite, by ferrosilicon process
industrial, sales 1298, 1299, 1303, 1304, 1305	for debismuthing lead, use prohibited, by War Production Board 763
prices 1311	war Production Board 763 foreign trade 767 778
	magnesite and dolomite deposits as source 776
production 1300 refractory, sales 1298, 1299, 1303, 1304 sales 1297, 1298, 1300, 1301, 1303, 1304, 1305, 1306, 1307	military requirements
sales, 1297, 1298, 1300, 1301, 1303, 1304, 1305, 1306, 1307	preference orders 775
salient statistics 1298 shipments 1308, 1309, 1310, 1311	priority control 772
shipments	primary, production
1908, 1909, 1310, 1311     Uses, trends	production, by Dow process 769 by electrothermic reduction 776
labor data 1297	by Hansgirg process 771 1404
men employed1547	salient statistics 767
	secondary, annual review 525' consumption 526
number 1312 Lime plants, capacity 1311, 1312	Drices
size1313 Lime-soda-sinter method, as source of alumina. 1329	recovery 521, 525, 526, 773
Lime-soda-sinter units, at aluminum plants	stocks       526         status, as critical mineral       768
War Production Board approval 606 l	technologic developments
Limestone, crushed, sales 1245, 1246	Magnesium-base alloy products consumption 774
sales	producers, list 7775 Magnesium carbonate, foreign trade 1501
fluxing, sales 1249 sales 1222, 1225, 1226, 1230 Limestone quarries, accidents 1540, 1547 men employed 1540, 1547	
Limitation orders War Production Board 80 199	Magnesium chloride, foreign trade 1501
Limitation orders, War Production Board 80, 128 Linseed oil, quota for paints, reduction 206 Litherra consumption	production, increase 1499 Magnesium compounds, annual review 1491
Esthaige, consumption	foreign trade 1492, 1501 production 1499
17 sales 207, 208, 209	production1499 sales1492, 1493
Lithium, uses	Magnesium hydroxide, production 1500
Lithium chloride, recovery, from spodumene	VISPRESUIM incendiary hombs artinguishing
concentrates 1502	with feldspar 1419 Magnesium industry, annual review 767
Lithium metal, allocation control	Magnesium oxide, extraction from olivine 777
Lithium minerals, review1530	Droduction, from magnesite investigation 778
shipments1530	Magnesium Diant, loan of silver by Defense
Lithium ores, control, by War Production	Plant Corporation 82, 769 Magnesium products, sales 774
Board	Magnesium scrap. See Magnesium, second-
production 1500	arv.
Lithopone, consumption 212 foreign trade 217, 1446	Magnesium sulfate, foreign trade 1501 production 1500
foreign trade 217, 1446	production 1500  Magnesium well, as source of potash salts, Bureau of Mines and Geological
217,1440   1444   1440   1444   1440   1444   1440   1444   1440   1446   146	Bureau of Mines and Geological
sales 207, 209, 1443	Survey investigations 1455 Maine, minerals, production 43, 45, 48, 59
Loans, to mining industry, Reconstruction	slate industry, review 1260, 1261 Malay States Unfederated beautite data 705 712
Finance Corporation 22	Malay States Unfederated housite date 705 719

Page	Page
Manchuria, molybdenum, data 664	Mexico, antimony, data 781, 791, 793 antimony ore, import licenses 783
	antimony ore, import licenses
manufactured by Bureau of Mines, Gov-	arsenic, white, data 760, 761
	Bateman-Juarez-Tellez agreement   178
Motale Deserve Co contracts	Dismuth, data
	chrysothe aspestos, deposit
	fuorener dete 1407 1408 1409
	fluorspar, data. 140, 140, 140, 140, 140, 140, 140, 140,
	load review 174, 175, 176, 177, 178
	mercury, data 713, 727, 728
	mica data 1463, 1474, 1476
Manganese industry, annual review 613  Manganese ore consumption 622	silver, review 121, 123 sulfur, data 1356, 1358
Manganese ore, consumption 622  Manganese ore, consumption 622  in manufacture of ferromanganese 605	sulfur, data 1356, 1358
III IIIaliulacture of lori of the same and same	
In Halmacture of Let 1	trade agreement, fluorspar, duty, reduction 1393,
imports 614, 616	
metallurgical, shipments 628 prices 628	zinc, review
prices622	zinc, review 198, 199, 200, 202  Mica, block, consumption 1467 built-up, production 1470 foreign trade 1463, 1464, 1472 ground, production 1468
	built-up, production1470
	foreign trade 1463, 1464, 1472
Marble, crushed, sales 1245	ground, production1465
foreign trade	sales 1466
1222, 1225, 1226, 1229	Metals Reserve Co., contracts 27, 1463
Marble quarries, accidents 1546	prices1470
men employed	price control 1471 salient statistics 1464
Maritime Commission, shipping facilities,	salient statistics 1464 scrap, sales 1464, 1465, 1466
Marble, crushed, sales       124b         foreign trade       1254         sales       1222, 1225, 1226, 1229         Marble quarries, accidents       1540, 1546         men employed       1540, 1546         Maritime Commission, shipping facilities, copper       128         Meryland, bituminous-coal industry, data       837, 837,	scrap, sales 1467 sheet, consumption 1467
Maryland, bituminous-coal industry, data 837,	production1464, 1474
852, 853, 856, 858, 803, 804, 808, 810, 810, 800, 801,	sales
982 883 895	b_titutos 14/0
iron ore, consumption 580	1463
ron ore, consumption 43, 48, 60 minerals, production 1453	Mica splittings, consumption 1407, 1408, 1409
1260 1261	stocks 1408, 1409
State industry, review	Michigan hituminous-coal industry, data 837.
Masonry cements, data1215, 1216 Masonry mortars, data1225, 1216	852, 853, 856, 858, 863, 864, 869, 870, 870, 880,
Massachusetts, gramte, sates 616, 617, 619 manganese ore, data 43 48 60	copper, production
	copper, production 136, 137, 138, 139, 297, 298, 303
	587. 591
Mercury, Conservation Order 713,714,715	magnesium plants 769, 772
Mercury, Conservation Order 713,714,715 consumption 713,714,715 deposits, investigations, Bureau of Mines	magnesium plants
deposits, investigations, Bureau of Willes	metals production, annual review
and Geological Survey 714	metals, production, annual review 303 minerals, production 43, 45, 48, 61
export control 714 724	motional god royriout
foreign trade 714, 724  Metals Reserve Co., contracts 27, 713	1132, 1133, 1134, 1140, 1150, 1151, 1152, 1154
Metals Reserve Co., contacts 717  prices 714, 717  price control 718, 714 777	
price control 714, 717	1037, 1038, 1039, 1046, 1060, 1064, 1065, 1068, 1070, 1071, 1095, 1096, 1100, 1101, 1106.
	1070, 1071, 1095, 1096, 1100, 1101, 1100.
	silver, production 85, 95, 97, 101, 297, 303 Midway-Wilcox contact, Coastal Plain, baux-
	ito denosite 689
toota 110	ite deposits 689 Millstones, foreign trade 1348
Mercury industry, annual review	review
Mercury saits, foreign trade. 725, 726  Metal mines, accidents 1544, 1545 men employed. 1540, 1544, 1545 Metals Reserve Co., agreement with War Supplies, Ltd. 28  Bataman, Ingraz, Tellez, agreement, for pur-	
Metal mines, accidents	Minerala consumption - 0
men employed War	domestic production, stimulation.
Metals Reserve Co., agreement with 28	foreign, research, objectives
Bateman-Juarez-Tellez agreement, for pur-	Government stock nile nurchases 21
chase of lead from Mexico 178	metallic, production 37 nonmetallic, production 38
honus navment for overproduction	nonmetallic, production
conner	prices, indexes 6 production, value 1, 2, 37, 41, 43
lood 100	production, value1, 2, 37, 41, 45
gine 182	Voiume
contracts for domestic ares	stocks strategic, investigations, Bureau of Mines 19
creation 26	Geological Survey 20
creation 26 imports, graphite 575 creation 675	Minaral garth nigments, domestic manuac-
	ture 1031
resale, antimony 783 stock-pile purchases, asbestos fiber 1424	foreign trade
Stock-pile purchases, aspestos noci	prices 1532
bauxite 690 bismuth 765	
ahramita 004	sales
128	review 1531, 1532 sales 1531, 1532 Mineral industries, accident data 9, 1539, 1541, 1549
100.4	
manganaga ara U1% U10	annuar review 7, 1539, 1540 employment data 7, 1539, 1540 labor, stabilization order 1155
mica	
minerals 20, 21, 25	Minoral Wool production
monazite sand	
	Mining engineers, as technical advisors to em-
mitmatan 1040	
sapphire	ment 33
zinc190	3.5:
zirconium concentrates 829	review
FIT WHITH WHOO IN COOR	•

Page	Page
Minnesota, manganese ore, data 616 617 619	Montana minerals production 42 45 40 an
minerals, production 43, 45, 48, 61 Minor metals, annual review 819	Mineral County, metals, production394,
Mint, Bureau of, manganese manufactured for.	mining industry, review
by Bureau of Mines 614 Mississippi, minerals, production 43, 48, 62	Missoula County, metals, production 394.
matural gas, data 1131,	395, 399, 402, 410
1132, 1133, 1134, 1140, 1150, 1152, 1154, 1158	moss agate, production 395, 399, 402, 410 natural gas, review 1131, 1132, 1133, 1134, 1141, 1150, 1151, 1152, 1154, 1158 ore classification
1132, 1133, 1134, 1140, 1150, 1152, 1154, 1158 petroleum industry, data 1036,	1132, 1133, 1134, 1141, 1150, 1151, 1152, 1154, 1158
1037, 1038, 1039, 1047, 1060, 1064, 1065, 1068,	ore, classification 395
1071, 1095, 1096, 1100, 1106. Missouri, bituminous-coal industry, data 837	Park County, metals, production 394, 395, 397, 398, 399, 402, 410
Missouri, bituminous-coal industry, data 837, 852, 853, 856, 858, 863, 864, 869, 870, 872, 875, 876,	petroleum industry, data1036,
883 886 805	1037 1047 1060 1064 1065 1069 1071 1005 1000
copper, production 135, 136, 139, 297 iron ore, data 589, 591 lead, production 169, 170, 297, 298, 305 lead-copper-iron deposit, occurrence of nickel	Phillips County materials 1
lead. production 169, 170, 297, 298, 305	rinings County, metals, production 394,
lead-copper-iron deposit, occurrence of nickel	phosphate rock, data 1364, 1373, 1374, 1375
and cobalt 646	phosphate rock, data 1364, 1373, 1374, 1375 Powell County, metals, production 394,
1   10   10   10   10   10   10   10	395, 397, 398, 399, 402, 410  pyrites, data 1359  Ravalli County, metals, production 394,
marble, sales 1233	Ravalli County, metals, production 204
metals, production, annual review	
minerals, production 43, 45, 48, 62	sanders County, metals, production 394,
natural gas, data 1131, 1133, 1134, 1141, 1150, 1152, 1154, 1156, 1158	
silver, production 85, 95, 97, 101, 297	silver, production
silver, production       85, 95, 97, 101, 297         zinc production       189, 297, 298, 305         Molybdenum, allocation       657	98, 99, 101, 102, 103, 109, 111, 113, 115, 116, 117
Molybdenum, allocation 657	sapphire, production
data, monthly study, Bureau of Mines 661 export control 658	205 207 200 200 400 475
in National Emergency steels, reduction 657	silver mines, list94 Summit Valley district, metals, production412 tungsten_data422
prices	Summit Valley district, metals, production 412
producers 659	tungsten, data 676, 679
production from wulfenite 661 salient statistics 657	180, 203, 304, 206, 207, 209, 200, 400,
shipments 657, 659	Morocco, antimony, data 701 702
war regulations 658	Moss agate, production 1511
Molybdenum industry, annual review 657 Molybdenum ere, foreign trade 662	Motor fuel, consumption 1095
Molybdenum ore, foreign trade	foreign trade 1030, 1072, 1085, 1087
ium 1533	Summit Valley district, metals, production 412 tungsten, data 676, 679 zinc, production 189, 393, 394, 396, 397, 398, 399, 400 Morocco, antimony, data 791, 793 Moss agate, production 1511 Motor fuel, consumption 1095 demand 1030, 1072, 1085, 1087 foreign trade 1072, 1085, 1087 prices 1072, 1085, 1087 production 1072, 1072, 1085, 1088 production 1072, 1077, 1079, 1085, 1088, 1088 rationing 1084, 1085
prices 1534	production 1072, 1077, 1079, 1085, 1086, 1088
stock pile     1534       uses     1534	shipments 1084, 1085
Montana, antimony, data 785	102 107, 1079, 1085, 1086, 1088   rationing   1084, 1085   shipments   1094   1085   1096
Beaverhead County, metals, production 394,	yields1090
395, 397, 399, 400, 403 bituminous-coal industry, data 837, 852, 853, 856,	N N
858, 863, 864, 869, 870, 876, 881, 882, 883, 896	k - k
Broadwater County, metals, production 394, 395,	Naphthalene, production 995, 996
397, 398, 399, 400, 403  Butte district, metals, production 412  Cascade County, metals, production 394, 398, 399, 400, 404	sales 1001 National Academy of Sciences, survey, aluminum resources
Cascade County, metals, production 394, 398	inum resources 1329
399, 400, 404	National Emergency steels, development 645
399, 400, 404 chromite, review 636 copper, production 135, 136,	molypuenum content, reduction
137, 138, 139, 393, 394, 396, 397, 398, 399, 400	National Selective Service, nonferrous metal workers, occupational deferment.
Deer Lodge County, metals, production 394, 395,	Natural gas, consumption 922 1128 1149 1152
397 399 400 404	Natural gas, consumption 922, 1128, 1149, 1152 in carbon-black plants 1180
Lewis and Clark County, metals, produc- tion	disposition 1131
Fergus County, metals, production 394, 395,	recovery of sulfur
397, 399, 400, 404	disposition 1130 production 1127, 1128, 1129, 1130, 1132 recovery of sulfur 1127, 1128, 1129, 1130, 1132 salient statistics 1128 shipments interstate 1128
Flathead County, metals, production 394,	1100
399, 400, 405 gold, production 85, 97,	treatment for natural pasoline 1198 1151
98, 99, 101, 102, 103, 109, 111, 113, 115, 116, 117, 391.	use, in dehydration 1134 Natural-gas companies, activities, regulation,
394, 395, 396, 397, 398, 399, 400.	Dy rederal Power Commission 1190
gold dredges 106 Granite County, metals, production 394, 394, 305 307 308 300 400 405	Natural-gas fields, developments 1134 Natural-gas industry, annual review 1127 Government received:
	Government regulation 1129
Jefferson County, metals, production 394, 395, 397, 398, 399, 401, 406	repressuring operations 1130 Natural-gas pipe lines, connection, War Pro-
395, 397, 398, 399, 401, 406	Natural-gas pipe lines, connection, War Pro-
Judith Basin County, metals, production 394, 398, 399, 401, 406	doction board order 1129
lead, production169.	developments 1160 drilling orders 1129
lead, production 169, 170, 393, 394, 396, 397, 398, 399, 400 lignite industry, data 837	drilling orders 1129 Natural-gas wells, number 1133
lignite industry, data 837, 852, 853, 858, 863, 864, 869, 870, 873, 876, 883, 896, 905	Natural gasoline, consumption 1167
Lincoln County, metals, production 394,	distribution 1162, 1167 markets 1162
395, 398, 401, 408	Drices 1161 1169
Madison County, metals, production 394.	production 1027, 1086, 1161, 1162, 1164, 1171 runs to stills 1077, 1079
395, 397, 398, 399, 401, 408 manganese ore, review616, 617, 619	runs to stills 1077, 1079
Meagher County, metals, production 394, 395, 402 metals, production, annual review 389	salient statistics 1162 stocks 1027, 1030, 1059, 1161, 1162, 1170
metals, production, annual review 389	technologic developments 117()
metallurgic industry, review	vields 1162 1171

Page	rage
Natural-gasoline industry, annual review 1161	New Guinea, gold, data 120, 126 New Hampshire, amethyst, production 1512
Nebraska, minerals, production 43, 48, 63 petroleum industry, data 1036, 1037, 1048, 1060, 1064, 1065, 1068, 1071, 1095, 1096,	New Hampshire, amethyst, production1512
petroleum industry, data 1036,	Mem   Maintent   Memory   Me
1037, 1048, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1106.	pegmatites, beryl content820
1100, 1106.   1373	New Jersey, iron ore, data589, 591
Nelsonite, deposit1373	minerals, production 43, 47, 48, 65
Nepheline syenite, fluxing properties 1419	zine, production189, 353, 355
foreign trade1418	New Mexico, bituminous-coal industry, data 837,
prices1419	002, 000, 000, 000, 001, 000, 010, 010,
price control	882, 883, 896.
production1418	Catron County, metals, production 443,
Nephrite jade, deposits	446, 447, 448, 449
production1511	Colfax County, metals, production 443,
Netherlands East Indies, bauxite, deposits 711	444, 446, 448, 449
tin, data746,747,753	conner production (35.
Nevada, antimony, data 785	136, 137, 138, 139, 441, 442, 443, 444, 445, 446,
Boulder City, Bureau of Mines station.	447, 448.
manganese, manufacture 614	Dona Ana County, metals, production 443.
Observabili County motols production 410	
Clark County, metals, production 419, 422, 424, 425, 426, 430	fluorspar industry
Clark County metals production 419.	gold, production 85.
422, 424, 425, 426, 430	97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116,
copper, production 135,	117, 441, 443, 444, 445, 446, 447, 448,
136, 137, 138, 139, 416, 419, 420, 422, 423, 424,	Grant County, metals, production 443,
	444, 446, 447, 448, 449
425, 426. Douglas County, metals, production 419, 422, 426	Guadalupe County, metals, production 443,
dumortispite production 1520	447, 448, 452
dumortierite, production 1529 Elko County, metals, production 422,	
422, 424, 425, 426, 430	helvite, deposit 819 Hidalgo County, metals, production 443,
Fernanda County motals modulation 400	446, 447, 448, 452
Esmeralda County, metals, production 422,	iron ore data 520 501
423, 424, 425, 426, 430	446, 447, 448, 452 iron ore, data
Eureka County, metals, production 419,	170, 441, 442, 443, 444, 445, 446, 447, 448
420, 427, 432	
Eureka County, metals, production 425, 427, 432, fluorspar, data 1405 gold, production 85, 97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116, 117, 416, 410, 490, 492, 493, 494, 495, 496	Lincoln County, metals, production 443, 444, 448, 453
gold, production 85,	T Ct matala production 449, 448, 400
97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116,	Luna County, metals, production
117, 416, 419, 420, 422, 423, 424, 425, 426. gold mines 93, 417 Humboldt County, metals, production 419, 419, 420, 420, 420, 420, 420, 420, 420, 420	magnesium plant 770
gold mines 93, 417	magnesium plant       770         manganese ore, data       616, 617, 620         metals, production, annual review       439
Humboldt County, metals, production 419,	manganese ore, data 010, 017, 020
422, 423, 424, 425, 427, 432 Lander County, metals, production 419,	metals, production, annual review 439
Lander County, metals, production 419,	metallurgic industry 445 minerals, production 43, 45, 48, 65
422, 423, 424, 425, 427, 433	minerals, production 43, 45, 48, 05
lead, production 169,	mining industry, review 444
170, 416, 419, 420, 422, 423, 424, 425, 426	minerals, production 43, 43, 43, 43, 43, 43, 43, 43, 43, 43,
Lincoln County, metals, production 419,	natural gas, review 1131,
422, 423, 424, 425, 427, 433	1132, 1133, 1134, 1142, 1151, 1152, 1154, 1158 ore, classification 444
Lyon County, metals, production 419, 420, 421, 425, 427, 424	Ofe, classification
	Otero County, metals, production 443, 447, 448, 454
magnesium plant         770           magnesium products, review         1495           manganese ore, data         616,617,620           mercury, data         720,721,723	petroleum industry, data
magnesium products, review1495	1037, 1038, 1048, 1000, 1004, 1000, 1000, 1010,
manganese ore, data	notash industry, review 1453
deposits, Bureau of Mines investigations 715	potash industry, review 1453 Santa Fe County, metals, production 443, 444, 446, 447, 448, 454
metals, production, annual review 415	444, 446, 447, 448, 454
motollyproie industry, review 420	Sierra County, metals, production 443,
minerale production 43 45 48 64	444, 446, 447, 448, 454
metallurgic industry, review 420 minerals, production 43, 45, 48, 64 Mineral County, metals, production 419,	silver, production 85,
	silver, production 85, 97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116, 117, 441, 442, 443, 444, 445, 446, 447, 448.
mining industry, review 419	117, 441, 442, 443, 444, 445, 446, 447, 448.
mining industry, review 419  Nye County, metals, production 419, 422, 423, 424, 425, 428, 434  ore, classification 420	Socorro County, metals, production 443,
422, 423, 424, 425, 428, 434	446, 447, 448, 455
ore, classification 420	tin resources. Bureau of Mines and Geologi-
	cal Survey investigations 736
422, 423, 424, 425, 428, 435	tungsten, deposits, Bureau of Mines investi-
silver, production85,	gations 675 zinc, production 189, 441, 442, 443, 444, 445, 446, 447, 448
97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116,	zinc, production 189,
117, 416, 419, 420, 422, 423, 424, 425, 426.	441, 442, 443, 444, 445, 446, 447, 448
Silver mines 94, 418	
Storey County, metals, production 419,	ilmenite, deposits, as source of titanium 811
422, 424, 429, 436	production 205
tin, deposit, Bureau of Mines and Geological	New York, emery, production
Survey investigations 736	lead, production169, 170, 353, 355, 356
tungsten, deposits, Bureau of Mines and	metals, production, annual review 355
Geological Survey investigations 674 review 676, 679	minerals, production 43, 45, 48, 66
review 676, 679	natural gas, review
turquoise, production 1511	1132, 1133, 1134, 1142, 1151, 1152, 1154, 1150,
Washoe County, metals, production 419,	1158.
422, 424, 425, 429	petroleum industry, data 1036,
422, 424, 425, 429	1158. petroleum industry, data1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071,
White Pine County, metals, production 419, 422, 423, 424, 425, 429	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106.
White Pine County, metals, production 419, 422, 423, 424, 425, 429	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106.
422, 424, 425, 429 White Pine County, metals, production. 419, 422, 423, 424, 425, 429, 436 zinc, production. 189, 416, 419, 420, 422, 423, 424, 425, 426	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106. pyrites, data 1359 silver, production 85, 97, 101, 353, 355, 356
422, 424, 425, 429 White Pine County, metals, production 419, 422, 423, 424, 425, 429, 436 zinc, production 189, 410, 419, 420, 422, 423, 424, 425, 426 New Caledonia, chromite, data 640, 643	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106. 1106, 1107,
422, 424, 425, 429 White Pine County, metals, production. 419, 422, 423, 424, 425, 429, 436 zine, production. 189, 416, 419, 420, 422, 423, 424, 425, 426 New Caledonia, chromite, data. 640, 643 640, 643	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106. 1359 silver, production 85, 97, 101, 333, 355, 356 slate industry, review 1280, 1281 titaniferous magnetite deposits, as source of
White Pine County, metals, production. 419, 425, 429, 425, 429, 436 2inc, production. 189, 422, 423, 424, 425, 429, 436 2inc, production. 189, 416, 419, 420, 422, 423, 424, 425, 428, 428, 428, 424, 425, 428, 428, 428, 428, 428, 428, 428, 428	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106. 1106, 1107,
422, 424, 425, 429 White Pine County, metals, production	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106. 1106, 1107,
White Pine County, metals, production. 419, 425, 429, 425, 429, 426, 427, 428, 424, 425, 429, 436 zine, production. 189, 416, 419, 420, 422, 423, 424, 425, 426 New Caledonia, chromite, data. 640, 643 nickel, data. 648, 650 nickel smelter, substitution of gypsum for sulfur. 1294 Newfoundland, fluorspar, data. 1409, 1410	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106. 1106, 1107,
## 422, 424, 425, 429  White Pine County, metals, production	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106. pyrites, data 1359 silver, production 85, 97, 101, 353, 355, 356 slate industry, review 1260, 1261 titaniferous magnetite deposits, as source of titanium and possible source of vanadium 668, 812 zinc, production 189, 353, 355, 356 New Zealand, asbestos, deposits 1433
White Pine County, metals, production. 419, 425, 429, 425, 429, 426, 427, 428, 424, 425, 429, 436 zine, production. 189, 416, 419, 420, 422, 423, 424, 425, 426 New Caledonia, chromite, data. 640, 643 nickel, data. 648, 650 nickel smelter, substitution of gypsum for sulfur. 1294 Newfoundland, fluorspar, data. 1409, 1410	petroleum industry, data 1036, 1037, 1038, 1049, 1060, 1064, 1065, 1068, 1071, 1095, 1096, 1100, 1101, 1106. 1109,

Page	Page
New Zealand, mica, data	Oil, competition from other sources of energy 834
New Zenand, mica, data. 144, 1476 sulfur, data. 1366, 1359 Nicaragua, gold, data. 119, 124 Nickel, foreign trade. 645, 647 Metals Reserve Co., contracts 27 production. 645, 646, 648 salient statistics. 645 secondary, annual review. 531 consumption 532	839, 842, 845
Nicaragua, gold, data	Oil burners, sales, restrictions 931
Motels Personne Co. contracts 97	shipments 931 Oilstones, foreign trade 1348
production 645, 646, 648	Oilstones, foreign trade 1348
salient statistics 645	sales1331, 1338
secondary, annual review531	sales       1331, 1338         Oil wells, number       1056         Oil-well cement, data       1216
exports	Oklahoma, bituminous-coal industry, data 837.
Metals Reserve Co., purchases 532	852, 853, 856, 858, 863, 864, 869, 870, 873, 875, 881,
prices 532, 533 price control 532 recovery 521, 531	882, 883, 897. lead, production169, 170, 297, 298, 312
recovery 521, 531	manganese ore, data
Stocks 533	metals, production, annual review
Nickel deposits, Bureau of Mines and Geo-	minerals, production 44, 45, 48, 68
logical Survey investigations 646	natural gas, review 1128,
Nickel industry, annual review 645	natural gas, review 1128, 1131, 1132, 1133, 1134, 1144, 1152, 1154, 1158 natural gasoline, data 1164,
Nickel scrap. See Nickel, secondary. Nickel smelter, substitution of gypsum for	natural gasoline, data1164, 1165, 1166, 1167, 1169, 1171
sulfur 1294	petroleum industry, data1036,
sulfur     1294       Nigeria, columbite, data     824       tin, review     740,753       760,763	1037, 1038, 1039, 1049, 1060, 1064, 1065, 1068
tin, review 746, 753	1070, 1071, 1095, 1096, 1100, 1106, 1117.
tungsten, data 683, 684	1 Zine, production 186, 189-297, 298-312
tungsten, data 683, 684 Niobium, annual review 823 Niobium ores, import control 823	Olivine, deposits 1534 extraction of magnesium oxide 777
Nitrates, natural, review 1522	extraction of magnesium oxide 777 prices 1535
purchases, Defense Supplies Corporation 1522	shipments 1534
stock pile	O'Mahoney Act, effect on petroleum industry_ 1033
Nitrate deposits, domestic 1522	Orange mineral, consumption 211
Nitrogen, war uses 1521 Nitrogen compounds, annual review 1521	foreign trade217
Nitrogen compounds, annual review 1521 inorganic, review 1522	sales       208, 209         Ore-dressing plants, accidents       1548         men employed       1540, 1548         Oregon, antimony, data       785
Nitrogen Gundards, annual review 1522 organic, review 1522 organic, uses 1524 synthetic, review 1523 Nitrogen Gundards, annual de-	men employed 1540, 1548
synthetic, review 1523	Oregon, antimony, data785
Nitrogen plants, capacity	I aspestos, droduction1426
Nonferrous-metal workers, occupational de-	Baker County, metals, production 460,
lerment	463, 464, 465, 467
Nonmetals, minor, annual review 1525 Nonmetallic-mineral mines, accidents 1545	beach sands, as source of chromite, mineral dressing 637
men employed 1540 1545	bituminous-coal industry, data 853.
men employed 1540, 1545 North Africa, lead, data 179	dressing 637 bituminous-coal industry, data 853, 864, 869, 889 858, 863, 864, 869, 889
zinc, review 203 North America. See Bahamas; Canada; Cen-	chromite, data 636 Coos County, metals, production 460, 465
North America. See Bahamas; Canada; Cen-	Coos County, metals, production 460, 465
tral America; Cuba; Greenland; Ja-	copper, production
maica; Mexico; Newfoundland; United States.	136, 138, 139, 458, 461, 462, 463, 464, 465
North Carolina, asbestos, review 1426	Curry County, metals, production
North Carolina, asbestos, review 1426 copper, production 135, 136, 353, 357 corundum, deposits, investigation 1342 gold, production 85, 95, 97, 101, 351, 353, 357	gold, production 85, 97, 98, 99, 101, 102, 103, 109,
corundum, deposits, investigation1342	111, 113, 115, 116, 117, 458, 460, 462, 463, 464, 465
gold, production	Grant County, metals, production 460,
effect of Gold-Mining Limitation Order. 357 granite, for abrasive use 1339	463, 464, 465, 467 Harney County, metals, production 460, 465
kyanite, production, difficulties 1529	Jackson County, metals, production 460, 460,
metals production annual review 357	463, 464, 465, 468
minerals, production 43, 45, 48, 67 silver, production 85, 97, 101, 353, 357 titanium ores, data 85, 97, 101, 363, 357 North Dakota, lignite industry, data 837,	Jefferson County, metals, production 469
silver, production 85, 97, 101, 353, 357	Josephine County, metals, production 460,
North Dekote lignite industry, date 927	463, 464, 466, 469
852, 853, 856, 858, 863, 864, 869, 870, 873, 875, 881,	Lane County, metals, production 470 lead, production 169, 458, 461, 462, 463, 464, 465
882, 883, 896, 905.	lead, production 169, 458, 461, 462, 463, 464, 465 Malheur County, metals, production_ 460, 466, 470
minerals, production 43, 48, 67 natural gas, data 1133, 1143, 1152, 1154, 1158	manganese ore, data 617,620 mercury, data 720, 721, 724 deposit, Bureau of Mines and Geological
natural gas, data	mercury, data
Norway, aluminum, review       706, 711         molybdenum, review       664         zinc, data       200, 203	Survey investigation 715
zinc. data 200. 203	matale production annual review 457
	metallyrgic industry, review 462 minerals, production 44, 45, 48, 69 mining industry, review 461
<b>O</b>	minerals, production 44, 45, 48, 69
O	mining industry, review 461
Oceania. See Australia; New Caledonia; New	ore, classification 461 silver, production 85, 97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116, 117, 458, 461, 462, 463, 464, 465
Guinea; New Zealand; Tasmania. Ocher, foreign trade1532	111 113 115 116 117 458 461 462 463 464 465
Office of Price Administration. See Price	Union County, metals, production 460, 466
Administration, Office of.	Osmiridium, foreign trade808, 809
Ohio, bituminous-coal industry, data	Osmium, foreign trade 807, 808, 809
852, 853, 856, 858, 863, 864, 869, 870, 873, 875, 876, 880, 881, 882, 883, 886, 897.	price804
880, 881, 882, 883, 886, 897. iron ore, consumption 580, 581	refined, recovery
magnesium plants 770 779	uses804
magnesium plants 770, 772 minerals, production 43, 45, 48, 68	P
natural gas, review1131,	-
natural gas, review 1131, 1132, 1133, 1134, 1143, 1151, 1152, 1154, 1156, 1158	Packaged fuel, binders
petroleum industry, data	manufacture, processes 1016
1096, 1100, 1101, 1106	plants, number 1018
sponge-iron plant, experimental, authoriza-	size
tion597	raw fuels 1019

Page	Page
Packaged fuel, salient statistics 1016	Petroleum asphalt, foreign trade 1072, 1120, 1190
supplies 922 value 1016, 1017	production 1072, 1120, 1186 sales 1185, 1186, 1187
Packaged-fuel industry, annual review 1015	salient statistics 1186 stocks 1072, 1120, 1186, 1187
Paints, containers, substitute materials 206 Palestine, sulfur, data 1359	stocks1072, 1120, 1186, 1187
Palestine, sulfur, data 1359 Palladium, consumption 806	Petroleum asphalt industry, annual review 1185
Palladium, consumption 806 foreign trade 801, 807, 808, 809	Petroleum coke, demand 1072, 1119
price	foreign trade 1072 production 922, 1072, 1119
salient statistics 801	stocks 1072, 1119
secondary, recovery 801, 804	yield 1074, 1119 Petroleum Coordinator, Office of, petroleum,
stocks 807 uses 804, 805	proration 1034
Paying contracts 1194	petroleum industry, regulation 1033
Paving asphalt, sales 1187, 1188 Pearl Harbor, loss of life from fumes of burning	Petroleum gases, liquefied, annual review 1172 distribution 1175
cork 1533	production 1121, 1166, 1168, 1171
Peat, annual review 1021	Sales       922, 1172, 1175         stocks       1162, 1170
production 1021, 1024 reserves 1021	uses 1172, 1175
uses 1023	Petroleum industry, annual review 1025
value	O'Mahoney Act, effect 1033 wartime regulation 1033
Pennsylvania, anthracite, production 857,	Petroleum Industry War Council, organiza-
915, 922, 935, 936, 937	tion17
shipments 938 See also Anthracite.	Petroleum operators, permission to obtain materials under Priorities Rating
anthracite industry, problems, research 913	Plan1034
anthracite regions 935	Petroleum products, refined, annual review 1071 demand, wartime, alterations of industry 1071
	foreign trade1030, 1123
bituminous-coal industry, data837, 852, 853, 856, 858, 863, 864, 869, 870, 873, 875, 876,	marketing, restrictions1054
880, 881, 882, 883, 886, 898.	miscellaneous, data 1072, 1120 production 1072, 1077, 1079
gold, production	runs to stills 1075, 1077, 1075
review590, 591 manganese ore, data616, 617, 620	salient statistics         1072           shipments         1125
metals production applied review 357	intercoastal 1126
minerals, production 44, 45, 48, 70	stocks
11331134. 1145. 1150. 1151. 1152. 1154. 1156. 1158	yields 1074
petroleum industry, data	Petroleum refineries canacity 1081
1037, 1038, 1031, 1000, 1004, 1003, 1008, 1070, 1071, 1095, 1096, 1100, 1101, 1106, 1117.	natural gas, consumption 1128, 1150, 1153, 1154 Petroleum wells, number 1056
pyrites, data1360	Phosphate rock, as source of vanadium 668
rottenstone, foreign trade1348	Bureau of Mines and Geological Survey
sales       1333, 1334         silver, production       85, 97, 101, 353, 357         slate industry, review       1260, 1261, 1262         1270       1372	consumption 1368
slate industry, review	distribution 1367
Peru, antimony, data 791, 794	prices 1368
arsenic, data	price control 1368 production 1363, 1364, 1366, 1377
chrysotile asbestos, deposit 1433	production 1303, 1304, 1300, 1377 sales 1364, 1367
copper, review 153, 161	salient statistics 1364
gold, data 119, 126 lead, data 174, 175, 177, 179	Tennessee Valley Authority investigations 1371 world trade, effects of war 1364
mercury, data 713, 727, 728	Phosphate-rock industry, annual review 1363
mica, data 1472, 1474, 1476 silver, data 121, 126 tungsten, data 681, 683, 684	Pig iron, consumption
tungsten, data681, 683, 684	foreign trade 570, 600 fuel efficiency 838
vanadium, facilities, construction, by Defense Plant Corporation 29	prices
review	production 509, 570, 571, 597, 503 salient statistics 544, 570
zinc, data	shipments 570, 597
Petroleum, demand 1025, 1026, 1030, 1035, 1064, 1065	
distribution 1062, 1068	Piggiron industry annual review 597
foreign trade 1030, 1123 prices 1069	
production 1026, 1027, 1036, 1121	production 164, 166 Pigments. See Iron oxide pigments; Lead pig-
proration1034	ments; Mineral earth pigments; Zinc
runs to stills 1062	pigments.
salient statistics 1027 shipments 1125	Pigments industry, annual review 205
intercoastal 1126	Pinite, sales 1383 Platinum, consumption 200
stocks1027, 1058	
supply 1030, 1035 transportation problem 1083	purchases
value	Metals Reserve Co., contracts
value	refined, recovery
functions	l colient statistics . OUI
organization 17 Petroleum asphalt, demand 1072, 1120	secondary, recovery 801, 804 stocks 807
distribution 1190	uses 804, 805

Page	Pag
Platinum industry, annual review 801 Platinum metals, consumption 806	Price Administration, price control, potash 1450
foreign trade 801, 807, 808, 805	sand 154
prices 804	silver 127
production 801	
properties 804	
refined, recovery 803, 804	
salient statistics 801 stocks 807	titamum pigments
uses 804	wwlol 90
Polonium, use 827	1 ZIUC
Portland cement, consumption 1203	
manufacture, electric power 1215	zine pigments
fuels1214	rationing, gasoline and fuel oil 108
prices1210 production1193, 1194, 1197, 1198, 1200	1 regulation, automobiles, use 100
review1197	of authority under
review 1197, 1198, 1200, 1205, 1206 shipments 1194, 1197, 1198, 1200, 1205, 1206 specifications 1105, 1216	Priorities. See War Production Board.
	I FIGURES BALLUS PIAD, OH OPERATORS POSSOS
Stocks 1194, 1198, 1201	Design to get scarce materials under 1039
supplies 1208 transportation 1208 Portland-cement clinker, production 1202, 1212 stocks	Production Management, Office of, titanium
Portland-cement clinker, production 1202 1212	pigments, pool, for reallocation 811 Production Requirements Plan, features 5
stocks 1202	1 roddenon requirements rian, leatures5
Portland-cement plants, capacity 1211	Production Requirements Plan, features
Halurai gas, consumption 1128, 1150 1153 1154	Pulpstones, review
Portland-puzzolan cements, data 1216	sales
Portugal, mica, data 1476	
pyrites, data1361, 1362 radium, production828	
tin, data 747.753	sales 1331, 1339 USes 1331, 1339
Potash, prices1450	Uses
price control	
salient statistics 1448	
Potash company, German control 1453 Potash industry, annual review 1447	Fuzzoian cements, data
Potash producers, list 1440	Pyridine, allocation, War Production Board 954
Potash salts, allocation control 1448	production 996 Pyrites, foreign trade 1351, 1360
Potassium salts, consumption 1448, 1451	
foreign trade 1448, 1455 production 1447, 1448, 1449, 1461	
production 1447, 1448, 1449, 1461	
sales 1448, 1449 stocks 1450	
Potassiim-sodium nitrate imports 1599	
Power Commission, Federal, regulation, nat-	sales 1382, 1383
ural-gas companies 1129	Pyrophyllite industry, annual review 1381
ural-gas companies 1129 Power plants, public utility, natural gas, con-	salient statistics
sumption 1128, 1150, 1153, 1154 Preference ratings. See War Production	
Board.	Q
Premiums, for overproduction of metals 22, 131,	Quartz, review1334
	Sales Crystols of States 1331, 1334
Prices, minerals, indexes 6	Quartz crystals, as strategic mineral, impor-
rice Administration, Office of, functions 15	I tance 1535
organization 16 premiums, chrome ore exports 633	I deposite
overquota production 22, 131, 165, 182	import control 1535  Metals Reserve Co., contracts 27  Ouertz pebbles imports
price control, aluminum 700	
secondary525	I Quartzite, foreign trade 1964
anthracite 926	i Wuartzite beddies, occurrence 1990
antimony 783	I Quickline, sales 1908 1200
secondary 540 arsenic compounds 759	Quicksilver. See Mercury.
brass, secondary 530	R.
cadmium 799	
cement1195	Radium, annual review 826
chromite ores 633	ioreign trade 826
coke, beehive 953 byproduct 954	I Drices
byproduct954 copper132, 134	USes 827
secondary 530	Railroad ballast, sales   1238, 1239   Range oil, consumption   921   sales   922, 1101, 1103, 1104   Raw Materials Board, Combined, creation   10
ferrous scrap 545 fluorspar 1393, 1398	sales 922 1101 1103 1104
fluorspar 1393, 1398	Raw Materials Board, Combined, creation 10
gravel1278	
gypsum 1283 jewelry 1513	Reconstruction Finance Corporation, authority, transfer to Board of Economic
jewelry	ity, transier to Board of Economic
lead, secondary 535	Warfare 30 financing, aluminum industry 696
lime1297	
magnesite1494	I to mining monstry 99 121
magnesium 768, 775	I DIFCHASE OF STRATEGIC MATERIALS by out on
secondary 526	thorizing 25
mercury714, 717 mica1471	transfer, from Federal Loan Agency 10
nepheline syenite1419	ried lead, consumption 210
nickel, secondary 532	10reign trade
phosphate rock 1368	sales 207, 208, 209 Research, foreign minerals, objectives 34

Page	Pag	ge
Rhode Island, minerals, production 44, 48, 70		43
Rhodesia, Northern, cobalt, review 654		$\frac{21}{2}$
copper, review 154, 159	Seybolite, uses14	28 28
vanadium, review 670		$\frac{28}{28}$
zinc, data		$\tilde{28}$
Southern, asbestos, data. 1430, 1431 Rhodium, foreign trade 807, 808, 806		$\widetilde{28}$
price804	sales8	28
refined recovery	stocks8	28
use, in jewelry, prohibition 801, 805		28
Road oil, demand 1072	Sienna, foreign trade15	
production1072	Silica abrasives, review 13	
review 1192	sales 13 Silica-stone products, review 13	
sales 1193	10	
salient statistics 119:	2	22
stocks 1073 yields 1074		06
Road metal, sales 1238, 1238	stocks 6	22
Rock salt sales 1477, 1479	Silicon carbide, sales 1345, 13	46
shipments 148: Roofing asphalt, sales 1187, 1188, 118	Sillimanite, deposit 15	29
Roofing asphalt, sales 1187, 1188, 118	Silver, consumption	83
Roscoelite ores, as source of vanadium 00	loreign, restrictions on purchase and use	90
Rottenstone, foreign trade 134		82
sales 1333, 1334	import control	83
Rubber, synthetic, use of magnesia from sea water149	Metals Reserve Co., contracts	27
Ruby mining methods 1513	prices 48,	86
Ruthenium, foreign trade 807, 808, 809	Drice control	82
price80	1 Droomelion, mine 31, 30, 1	01
price	Mint report	92 85
usesou		
Rutile, consumption 81 imports, control 81		83
prices 81	salient statistics	80
prices	stocks supply, domestic	87
stocks81	supply, domestic	91 88
a a	silver bullion, Government-owned, lease, by	. 00
<b>.</b>	Defense Plant Corporation 82,7	769
Safety records, annual data	Silver industry, annual review	79
Salines, annual review 150	l labor data	107
Salt, demand, seasonal 148	, original despotation of the second of the	118 544
distribution 148	looding list	94
foreign trade1477, 149 production147	leading, list	544
plant capacity148	number	95
resources 148	Silver ore, production	90
sales 1477, 147	Silver Users Emergency Committee, formation	83 379
salient statistics 147	Slag, Dasic, Gata	280
shipments 148 stocks 148	)   sales	282
uses       148         Salt blocks, sales       148	Slag-lime cements, data1	217
Salt cake, prices150		40 <i>1</i> 263
Salt industry, annual review 147		259
Salt industry, annual review 147 Salt plants, list, changes 148	roofing percentage utilization 15	263
Sand, abrasive, review	salient statistics 12 waste, use as aggregate, Bureau of Mines	256
foreign trade 127	waste, use as aggregate, Bureau of Mines	000
ground, review133	study1256 1258 12	262 250
sales		25
preparation, degree 127		
price control 127	S   Slate quarries, accidents	540
		n41
production 1267, 127	men employed1540, 18	21
production 1267, 127 sales 1266, 1267, 1268, 127	6 men employed 1540, 16 8 Slip clay, sales 12 4 Should War Plants Corporation greation	31
production	3   Slip clay, sales	31
production 1267, 127, 127, 128, 127, 1288, 127, 1288, 127, 1288, 127, 1289, 127, 1289, 127, 12890, 1289, 1289, 1289, 1289, 1289, 1289, 1289, 1289, 1289, 1289, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 12890, 128	3   Slip clay, sales	31
production	3   Slip clay, sales	31
production	3 Slip clay, sales	31
production	3 Slip clay, sales   14	31 54 54 54 38 38 38
production	3   Slip clay, sales	31 54 54 38 38 38 38
production	Slip clay, sales	31 54 54 38 38 38 38
production	3   Slip clay, sales   1   4   5   maller   War Plants Corporation, creation   5   5   men employed   1540, 14   3   Soapstone, ground, annual review   1387, 1388, 1   6   foreign trade   1387, 1388, 1   1   prices   1   1   5   sales   1382, 1   1   5   sales   1382, 1   1   5   sales   1382, 1   1   1   1   1   1   1   1   1   1	31: 54: 54: 38: 38: 38: 38: 38: 50:
production	3   Slip clay, sales   1   4   5   maller   War Plants Corporation, creation   5   5   men employed   1540, 14   3   Soapstone, ground, annual review   1387, 1388, 1   6   foreign trade   1387, 1388, 1   1   prices   1   1   5   sales   1382, 1   1   5   sales   1382, 1   1   5   sales   1382, 1   1   1   1   1   1   1   1   1   1	31: 54: 54: 38: 38: 38: 38: 50: 50:
production	Slip clay, sales   1	31: 54: 54: 38: 38: 38: 38: 50: 50: 69:
production	Silip clay, sales	31; 54; 54; 38; 38; 38; 38; 50; 69; 69;
production	Slip clay, sales	31: 54: 54: 54: 38: 38: 38: 38: 50: 69: 75: 50:
production	Slip clay, sales	31: 54: 54: 38: 38: 38: 38: 38: 50: 50: 50: 50: 50: 50: 50: 50:
production	Slip clay, sales   1	31 54 54 38 38 38 38 38 50 50 50 50 50
production	Silip clay, sales	31 54 54 38 38 38 38 38 38 50 50 50 50 50
production	Silip clay, sales	31 54 54 38 38 38 38 38 50 50 50 50 50 50
production	Silip clay, sales	31 54 54 38 38 38 38 38 38 50 50 50 50 50

Page	Page
Sodium phenolate, production 996 Sodium sulfate, prices 1507	Steel construction, paint requirements 206 Steel Formula, Little, adoption, for settling
review1505	wage disputes 572
sales	Steel furnaces, electric, ferrous scrap and pig
uses 1506	iron, consumption 552, 556 Steel industry, annual review 607
Solders, tin content, reduction735 Solid Fuels Administration for War, creation_ 11, 918	men employed 572 wages, increase 572
functions	Steel ingots, manufacture 607, 608
organization 18 Solid Fuels Advisory War Council, organiza-	Steel manufacture canacity 607.608
Solid Fuels Advisory War Council, organiza- tion	Steel products, foreign trade 610 Steel scrap, consumption 544, 550
Solid Fuels Coordination for National Defense.	Steel scrap, consumption 544, 550 in ferro-alloys 562
Office of, establishment 18,918 Solid Fuels Coordinator for War, Office of,	foreign trade564 inventories, increase, permission546
Bureau of Mines cooperation with 913	price control
establishment 18,918 South America. See Argentina; Bolivia; Brazil; British Guiana; Chile; Colom-	salient statistics 544 stocks 544, 546
South America. See Argentina; Bolivia; Brazil; British Guiana; Chile; Colom-	tariff, suspension, legislation 546
bia; Ecuador; Peru; Surinam; Vene-	Steel scrap industry, annual review 543
South Carolina, gold, production	Stellite, cobalt in, use 653 Still gas, production 1077, 1079
zuela. South Carolina, gold, production	Stocks, control Stock piles. See Metals Reserve Co., stock
metals, production, annual review 357 minerals, production 44, 48, 71 silver, production 85, 97, 101, 853 South Dakota, beryl, sources, search 820 copper, production 472, 473 Custer County, metals, production 474 gold, production 85, 97, 98, 99, 99, 101, 102, 103, 104, 105, 116, 116, 116, 117, 473, 473, 474	nile nurchases
silver, production 85, 97, 101, 353	Stone, crushed, annual review 1237
conner production 472, 473	markets 1252 plants 1240
Custer County, metals, production 474	sales1222, 1223, 1237
gold, production 85, 97, 98, 99, 101 102 103 109 115 116 117 472 473 474	foreign trade 1253
101, 102, 103, 109, 115, 116, 117, 472, 473, 474 Homestake mine, gold, production 473, 474	sales 1221, 1222
Lawrence County, metals, production 473, 474	Stone industries, annual review 1221 Stoneware clay, sales 1317, 1322
lignite industry, data 837,	sailent statistics
853, 856, 858, 863, 864, 869, 874, 875, 883, 899, 907	Strategic Materials Act, passage 25 Strategic minerals, stock pile, list 21
Lawrence county, means, production. 169, 472, 473 lignite industry, data 837, 853, 856, 858, 863, 864, 869, 874, 875, 883, 899, 907 manganese ore, data 616, 617, 620 metals, production, annual review 471	See also these minerals in this index.
metallurgic industry 473 minerals, production 44, 45, 48, 71	Strontium minerals, data 1536 Sulfate-resisting cement, data 1216
mining industry 473	Sulfur, byproduct, recovery from ores 1352
mining industry 473 natural gas, data 1133, 1146, 1150, 1152, 1154 Pennington County, metals, production 473, 476	consumption 1354 foreign trade 1351, 1355
silver, production 85, 97, 98, 99,	Sulfur, price 1351, 1353
silver, production. 85, 97, 98, 99, 101, 102, 103, 109, 115, 116, 117, 472, 473, 474 zine, production. 189, 472, 473 South-West Africa, beryl, data 221	Sulfur, price         1351, 1353           price control         1353           production         1353
South-West Africa, beryl, data 821	recovery, from natural gas 1353
gem stones, review1519	salient statistics 1351
South-West Africa, beryl, data   September	stocks 1351, 1353 war aspects 1349
bismuth, data	Sulfur industry, annual review 1349, 1351 Sulfuric acid, allocation 1350
lead, data 177, 179 mercury, data 727, 728	as byproduct of zine smelting 187
pyrites, data1361, 1362	consumption 1355
sulfur, data1309 tin_data1747.753	price control 1353
titanium, data     818       zinc, data.     198, 200, 204       Spiegeleisen, consumption     622       foreign trade     570, 606, 614, 624	recovery, at smelters 1351, 1352
Zinc, data198, 200, 204 Spiegeleisen_consumption 622	Sulfuric-acid manufacturers, indictment charg- ing violation of antitrust laws 1350
foreign trade 570, 606, 614, 624	Superphosphates, foreign trade
	Superphosphates industry, salient statistics 1378 Surinam, bauxite, foreign trade
price 627 production 604, 605, 614, 626 shipments 570, 604, 626	Surinam, bauxite, foreign trade 711 Sweden, aluminum, review 706, 711 arsenic, white, data 760, 760
shipments 570, 604, 626 stocks 622	
Spodumene concentrates, recovery of lithium	fluorspar, data 1410
chloride 1502 Sponge iron, as substitute for scrap 597	fluorspar, data 1410 lead, data 176, 176 pyrites, data 1361, 1365 sulfur, data 1356, 1355 Switzerland, aluminum, data 706, 712
Sponge-iron plant, experimental, authoriza-	sulfur, data1356, 1359
tion597	Switzerland, aluminum, data 706, 712
State Department, Bateman-Juarez-Tellez agreement, for purchase of lead from	T
Mexico 178 war work, foreign 31	Taggers tin, foreign trade
Statistical summary, mineral production,	Talc, Bureau of Mines investigations 1386
annual 35 Steam railroads, fuel efficiency 838	conservation order1387   foreign trade1387, 1388, 1388
Steatite talc, conservation order 1382	markers 150°
definition 1385 foreign trade 1387, 1388, 1389	prices 1388 sales 1382, 1383
stock piles	
1385	statistics 1386 steatite, stock piles 1386 Talc dust, as occupational hazard 1386
permissible 1382 Steel, fuel efficiency 838	Tale dust, as decorpational nazard
National Emergency, development 645	Tale industry, annual review 1381 developments 1381 Tantalite, imports 82
production 570, 607 salient statistics 570	snipments 024
Steel costings manufacture 607 608	Tentelite-columbite production 82

Doga l	Page
Page	
Tantalum, allocation control 823	Tin, secondary, annual review 536
annual review	prices 538
Tantalum Defense Corporation, financing 823	price control 538
The state of the s	products, production 534
production 823	recovery 521, 536, 732, 737
Tantatum metal, prices   823   Production   823   Rar, production   823   Tar, production   956, 992, 994, 996, 999   Sales   999   Pasmania, gold, data   120, 126   Tellurium, annual review   828	Consumption
Tar, production 956, 992, 994, 996, 999	StOCKS         331,745           stocks         731,745           Tin Buffer Pool, liquidation         748           Tin Committee, International, agreements         28           Pin contract colders, degreedation         28           Pin contract colders         275
sales999	Tin Buffer Pool, liquidation 748
Tasmania, gold, data120, 126	Tin Committee, International, agreements 28 Tin content, solders, degradation
Tellurium, annual review 828	Tin content, solders, degradation
prices 828 production 828	Tin deposits, investigations, Bureau of Mines
uses 829	and Geological Survey
Tennessee, barite, data 1437	Tin industry, annual review
bituminous-coal industry, data 837,	world espects 746
852, 853, 856, 858, 863, 864, 869, 870, 876, 880, 881,	Tin manufactures, foreign trade 742
882, 883, 886, 899.	Tin ore, purchases, Government
copper, production	Tin plate, degradation 735 foreign trade 742
fluorspar, data 1406	foreign trade 742 Tin Scheme, International, abandonment 28
gold, production85, 97, 101	Tin screp. See Tip secondary
iron ore, data591	Tin Scheme, International, abandonment 28 Tin scrap. See Tin, secondary. Tin smelter, Government, status 733
lead, production	Titanium, consumption 814
manganese ore, data oro, orr, 020	Titanium, consumption 814 foreign trade 813
gold, production 85, 97, 101 iron ore, data. 591 lead, production 169, 353 manganese ore, data. 616, 617, 620 metals, production, annual review 358 minerals, production 44, 45, 48, 72	prices 816
natural gas, data 1133, 1134, 1146, 1150, 1152, 1154	technologic developments
nhosphate rock review 1364, 1369, 1371	Titanium alloys, uses 815
pyrites, data 1360 silver, production 85, 97, 101 zinc, production 189, 353 Tennessee Valley Authority, investigations, 1371	Titanium concentrates, production 812, 817 stocks 814
silver, production 85, 97, 101	
zine, production189, 353	Titanium industry, annual review 811
Tennessee Valley Authority, investigations,	Titanium pigments, pool, for reallocation by Office of Production Management
phosphate rock	prices 812
Terneplate, foreign trade 742 Texas, bituminous-coal industry, data 837 Texas, bituminous-coal industry, data 837	production 815
852, 854, 856, 858, 863, 864, 869, 883, 899	restrictions, lifting
Brewster County, metals, production 478, 479	uses815
conner, production 135, 136, 138, 139, 478	Toluol, allocation, War Production Board 954
Culberson County, metals, production 478, 479	price control
flint pebbles, deposits     1338       fluorspar, data     1399, 1406       fuller's earth, production     1325	Trade agreement, Mexico, fluorspar, duty,
fluorspar, data1399, 1406	reduction 1393, 1408
fuller's earth, production	reduction 1393, 1408 Trap rock, crushed, sales 1243, 1244
gold, production 85, 97, 98, 99, 101, 102, 103, 113, 115, 117, 478	Trap rock, crusned, sales
	Trap-rock quarries, accidents 1546
Hudspeth County, metals, production 478, 480 iron ore, data	men employed 1540, 1546
lead, production 169, 478	Travertine, foreign trade
lignite industry, data 837,	Treasury Department, Procurement Division, stock-pile purchases 25
852, 854, 856, 858, 863, 864, 873, 883, 899, 907	Tremolite denosits 1424, 1426
	Tremolite, deposits 1424, 1426 Tripoli, foreign trade 1348
magnesite, data.     1496       magnesium plants     769       manganese ore, data.     616, 617, 620       mercury, data.     720, 721, 724       metals, production, annual review     477       minerals, production     44, 45, 48, 72       ratural gas, review     1128, 1131, 1132, 1133, 1134, 1146, 1150, 1151, 1152, 1154, 1159       natural gasoline, data     1164	prices 1334
manganese ore, data	review1333
mercury, data	Sales 1001, 1000
minarels production 44 45 48 72	USES 1334 Trona, sales 1505
natural gas, review	Trona, sales       1505         Tube-mill liners, review       1338
1132, 1133, 1134, 1146, 1150, 1151, 1152, 1154, 1159	
natural gasoline, data1164,	Tungsten, deposits, Bureau of Mines and
1165, 1166, 1167, 1169, 1171	(leological Survey investigations 0/4
ore, classification 478	foreign trade 681
ore, classification 478 petroleum industry, data 1020 1024 1025	Metals Reserve Co., contracts28
1037, 1038, 1039, 1051, 1060, 1064, 1065, 1068, 1070, 1071, 1095, 1096, 1100, 1101, 1106, 1107.	Tungsten concentrates, prices 675
Presidio County, metals, production 478, 480	production 673, 675 salient statistics 673
refining plants	shinments 673, 676
refining plants 479 silver, production 85,	Tungsten industry, annual review
97, 98, 99, 101, 102, 103, 113, 115, 117, 478	Tungsten mine, as source of molybdenum 660
smelting plants 479	Tungsten are imports 681
sulfur, production 1351, 1352	prices 675 production 673, 675
tin smelter, Government, status 733 tungsten, data 676, 680	production673, 675
tungsten, data676, 680	salient statistics 673 676
volcanic ash, deposits 1341 zinc, production 478	Tunicia lead industry 179
Thallium, prices 829	sainent states         673,676           shipments         673,676           Tunisia, lead industry         179           Turkey, antimony, data         791,794           obroprite data         640,643
Thallium sulfata usas 820	chromite, data 640, 643 chrysotile asbestos, deposit 1434 manganese ore, data 629
Thorium, uses 1534 Thylox process, for recovery of sulfur from	chrysotile asbestos, deposit1434
Thylox process, for recovery of sulfur from	manganese ore, data629
natural gas	Turquoise, production 1511
l'in, conservation 732, 734	$\mathbf{v}$
exports control 721	J
foreign trade 732.741	Umber, foreign trade 1532
Metals Reserve Co., contracts 28	Union of Socialist Soviet Republics, asbestos,
prices	data 1429, 1430, 1432
1	chromite, data 644 Defense Supplies Corporation contracts 29
smelter 732, 737 salient statistics 732	Defense Supplies Corporation contracts
	IIIAIIEALIOSO UI C. USIA

Page	Page
Union of Socialist Soviet Republics, mercury,	Utah, silver producers, list94
data714, 727, 729	sulfur, deposit 1352 Summit County, metals, production 485,
mica, data1476	Summit County, metals, production 485,
nepneline syenite, deposit 1419 potash, foreign trade 1448	1 488, 490, 492, 498
pyrites, data 1362	Tintic district, metals, production 493 Tooele County, metals, production 485,
sulfur, data1359	488, 490, 492, 500
pyrites, data 1362 sulfur, data 1359 tin, data 733, 754	488, 490, 492, 500 tungsten, data 676, 680 deposits, Bureau of Mines Investigations 675
Union of South Africa, asbestos, data 1429,	deposits, Bureau of Mines Investigations 675
1430, 1431 fluorspar, data1409, 1410	Uintah County, metals, production 485, 492 Utah County, metals, production 485, 490, 492, 502
gold, data120, 126	vanadium ore, deposits 666
magnesite, data 1407	variscite, production 1512
manganese ore, data 630	Wasatch County, metals, production 485,
mercury, data727, 729	488, 490, 492, 498
manganese ore, data     630       mercury, data     727, 729       platinum metals, data     810       tin, data     747, 753	Washington County, metals, production 485,
United Kingdom, aluminum, data 706 712	Wayne County, metals, production 490, 492, 502 485, 490, 492, 502
United Kingdom, aluminum, data 706, 712 arsenic, data 760, 761 barite, data 1439, 1440	490, 492, 502
barite, data1439, 1440	west Mountain district, metals, production. 496
Dismutin, data	zine, production 189, 482, 484, 486, 487, 488, 489, 490, 491
chromite, data 644 ferrous scrap, data 564,566	102, 101, 100, 101, 100, 101, 101
magnesium, data 778,779	${f v}$
magnesium, data	
titanium, data	Vanadium, deliveries and melting, War Pro-
United States, mineral products	duction Board control 666
functions 28	Metals Reserve Co., test work, financing 28
Uranium, foreign trade 826	phosphate rock as source, Bureau of Mines and Geological Survey studies
prices	prices 666
uses	production665, 666
in ceramics, prohibited by War Produc- tion Board	recovery, from ilmenite tailings, Bureau of Mines study 816
tion Board	Mines study 816 salient statistics 665
Utah, alunite, as source of potash, Bureau of	titaniferous magnetite deposits as possible
Mines investigations 1454	source668
Beaver County, metals, production 485,	uses 666
488, 489, 490, 491, 493	Vanadium industry, annual review 665 Vanadium ore and concentrates, foreign trade 665,
Bingham district, metals, production————————————————————————————————————	669
858, 863, 864, 869, 870, 876, 881, 882, 883, 899	Variscite, production 1512
Box Elder County, metals, production 485,	Venezuela, chrysotile asbestos, deposit1433 gold, data119, 126
490, 491, 493 copper, production135, 136, 137,	magnesite, data1497
138, 139, 482, 484, 486, 487, 488, 489, 490, 491	vanadium, soot as source 672
fluorspar, data 1399, 1406 gold, production 85,	Vermiculite, prices 1537
gold, production 85,	sales1536 war uses1536
97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116, 117, 482, 485, 487, 488, 489, 490, 491.	Vermont, asbestos, production 1426
Grand County, metals, production 485 401 l	copper, production 360
Iron County, metals, production 485.	granite, production
489, 490, 491, 493	minerals production 44 45 48 74
data500 501	slate industry, review1260, 1261
489, 490, 491, 493   494   495   496   491, 493   495   49	Slate industry, review   1260, 1261
488, 489, 490, 491, 493 i	Dituminous-coal industry, data 837,
lead, production 169,	
170, 482, 484, 486, 487, 488, 489, 490, 491	copper, production 135, 136, 353, 360, 361
magnesium well, as scurce of potash salts, Bureau of Mines and Geological Sur-	gold, production85, 97, 101, 353, 360, 361
Vev investigations 1455 1500 I	copper, production 135, 136, 353, 360, 361 gold, production 55, 97, 101, 353, 360, 361 iron ore, data 500, 591 kyanite, production, difficulties 1529
manganese ore, data 616, 617, 620 metals, production, annual review 481	lead, production 169 353 360 361
metallurgic industry, review 487	manganese ore, data 616, 617, 620
Millard County, metals, production 485,	lead, production
490, 491, 496	natural gas, data1133,
Morgan County metals production 44, 45, 48, 73	1147 1150 1152 1155 1156 1159
Millard County, metals, production 485, 490, 491, 496 minerals, production 44, 45, 48, 73 Morgan County, metals, production 485, 490, 491, 496 mining industry, review 490, 491, 496	nelsonite, deposit 1373 pyrites, data 1360 silver, production 85, 97, 101, 353, 360, 361
mining industry, review 486	pyrites, data 1360
natural gas, data 1133, 1147, 1150, 1152, 1154, 1159	titanium oraș data 819
ore, classification 486 Park City region, metals, production 498	titanium ores, data
phosphate rock, data1364, 1374, 1375	,
Plute County, metals, production 485.	w
188, 489, 490, 491, 496	77. 1 1 0 1 1 7
potash industry, review 1454 Salt Lake County, metals, production 485.	Wad ore, beneficiation, study 618 War Department, furloughs, for mine work 8
488, 490, 491, 496	War Department, furloughs, for mine work 8 War Information, Office of, creation
San Juan County, metals, production 485,	war materials, statistics, release forbidden_ 130
490, 491, 498	War Labor Board, National, Little Steel For-
400 402 408	mula, adoption 572
silver, production 97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116,	War Manpower Commission, creation 10 labor stabilization order 8
97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116,	War materials, statistics, release forbidden, by
117, 482, 483, 485, 487, 488, 489, 490, 491,	Office of War Information 130

	Page	Page
Var minerals, procurement, international		Washington, fluorspar, data 1399, 1406
aspects, annual review	25	Washington, fluorspar, data1399, 1406 gold, production 85, 97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116, 117, 504, 506, 507, 508, 509, 510,
Var Mobilization, Office of, functions	11	111, 113, 115, 116, 117, 504, 506, 507, 508, 509, 510,
Var organization, Government, annual review		511, 512. Grant County, metals, production506, 507, 512, 514
review	10	Grant County, metals, production 507 512 514
Var plants, construction, program, con- tinuation	6	iron ora data 590 591
Unuation Board allocation control	0	iron ore, data
Var Production Board, allocation control, ammonia	1523	
ammonium sulfate 954	1523	lead, production 169, 504, 505, 506, 507, 508, 509, 510, 511, 512, magnesite, data 1496
antimony	783	510, 511, 512.
arsenic	757	magnesite, data     1496       magnesium plants     772       manganese ore, data     616, 617, 620       metals, production, annual review     503
hongol	954	magnesium plants 772
casein, for paintscopper chemicals	206	manganese ore, data
copper chemicals	141	metals, production, annual review
cryolite	1411 1524	minerals production 44 45 48 76
cyanamid	823	mining industry review 507
ferrocolumbium	826	natural gas. data 1133, 1147, 1150, 1152
moly bdenum	657	metally production, annual review
notesh salts	1448	509, 510, 511, 512, 514
nyridina	954	ore, classification507 Pend Oreille County, metals, production 506,
sodium nitrate	1524	Pend Oreille County, metals, production 506,
culturic acid	1350	1 509.500.511.512.514
tantalum	823	silver, production 85, 97, 98, 99, 101, 102, 103, 109, 111, 113, 115, 116, 117, 504, 505, 506, 507, 508, 509,
	954	111, 113, 110, 110, 117, 504, 505, 500, 507, 508, 509,
xylol	954 182	510, 511, 512. Snohomish County metals production 506.
zine	102	Snohomish County, metals, production 506, 507, 509, 510, 511, 512, 515
approval, lime-soda-sinter units, at alumi- num plants	696	Stavens County metals production 506
conservation order, amosite, restriction	1424	509. 510. 511. 512. 515
nonessential building, stoppage	1283	
steatite talc	1382	whatcom County, metals, production 500,
steatite talccontrol, chromium products, delivery	632	509, 510, 511, 512, 516
	1530	Yakima County, metals, production 506, 511, 512, 516
quartz crystals scrap-metal imports	1535	zinc, production 189,
scrap-metal imports	546 666	504, 505, 506, 507, 508, 509, 510, 511, 512
vanadium deliveries and melting zinc, supply	182	Water nower competition from other sources
Copper Branch, organization	130	of energy 839, 842, 843 Wax, demand 1072, 1117 foreign trade 1072
stotoment on conner requirements	129	Wax, demand 1072, 1117
creation creation expansion programs, magnesium functions	10	foreign trade 1072
expansion programs, magnesium	769	price1118
functions	12	production 1072, 1118 stocks 1072, 1118
inventory restrictions, limente, removar	811	Stocks
limitation orders, copper	128	yields
gold mines magnesium for debismuthizing lead, use	80	852 854 857 858 863 864 869 870 875 876 880.
magnesium for depisimutifizing lead, use	763	852, 854, 857, 858, 863, 864, 869, 870, 875, 876, 880, 881, 882, 883, 886, 901.
prohibitedorder, connection of natural-gas pipe lines_	1129	manganese ore, data 616, 617, 621 minerals, production 44, 45, 48, 76
organization		minerals, production 44, 45, 48, 76
organizationpreference rating, effect on oil operators	1034	
	110	1132, 1133, 1134, 1148, 1150, 1151, 1152, 1155, 1159 petroleum industry, data 1036, 1037, 1054, 1060, 1064, 1065, 1068, 1071, 1095, 1096,
premiums, for overproduction of metals	21,	petroleum industry, data 1050,
131, 10		1100, 1106.
priorities, aluminum	704 540	Whetstones. See Oilstones.
antimony, secondary bauxite	705	White lead consumption 210
cadmium	795	foreign trade 217 sales 207, 208, 209 White and account data
copper	133	sales207, 208, 209
heal	164	white portiand tement, data 1210
magnesium	773	Wire communications industry, copper, sav-
zinc. secondary	542	ings128 Wisconsin, fuel briquets, production1008
prohibition of use of uranium in ceramics	826	iron ora data 590 591
quotas, copper	131 783	iron ore, data 590, 591 lead production 169, 170, 297, 298, 315 metals, production, annual review 315
reclassification, antimonyreduction, linseed-oil quota for paints	206	metals, production, annual review 315
scrap inventories, increase, permission	546	minerals, production 44, 48, 77
shipments fluorspar supervision	1392	minerals, production
sponge-iron plant, experimental, authoriza-		zinc, production 189, 297, 298, 315
tion	597	Witherite, imports 1436, 1443
war activities, foreign	33	
War Supplies, Ltd., agreement with Metals		production 1442 salient statistics 1436
Reserve CoWashington, antimony, data	28 785	Witherite industry, annual review 1435, 1442
Washington, antimony, data	506,	Wulfenite, production of molybdenum from 661
Asotin County, metals, production	07, 512	Wurtzilite, sales
Benton County, metals, production	506.	Wyoming, Albany County, metals, production 518
	J/, D1Z	Wurtzilite, sales 118.0 Wyoming, Albany County, metals, production 518 bituminous-coal industry, data 837, 852, 854, 857, 858, 863, 864, 869, 870, 874, 876, 881, 882, 883, 903
hituminous-coal industry, data 83	7.852.	857, 858, 863, 864, 869, 870, 874, 876, 881, 882, 883, 903
854, 857, 858, 863, 864, 869, 870, 876, 881, 88	2, 883,	
886, 900,		Copper, production 135, 130, 138, 139, 318
Chelan County, metals, production	_ 006,	copper, production 135, 136, 138, 139, 518 Crook County, metals, production 518, 519 Fremont County, metals, production 518, 519
507, 509, 510, 511, 5	12, 513	gold, production 85, 95,
copper, production 135, 136, 138, 139, 504, 50 507, 508, 509, 510, 51	0,000,	97, 98, 99, 101, 102, 103, 116, 117, 518
Douglas County, metals, production 506, 5	07, 512	Goshen County, metals, production 511
Ferry County, metals, production	506,	iron ore, data599
509, 510, 511, 5	12, 513	Johnson County, metals, production 518, 519
	-	

Page	P	age
Wyoming, lead, production 169, 518	Zinc, smelting, sulfuric acid as byproduct	187
metals, production, annual review 517	stocks182	190
minerals, production 44, 45, 48, 78	stock pile	190
natural gas, review 1128, 1131, 1132, 1133, 1134,	uses, conservation	181
1148, 1150, 1151, 1152, 1155, 1159.	Zinc chloride, consumption	214
nephrite, production1511	foreign trade	217
Park County, metals, production 520	sales 200	210
petroleum industry, data 1036, 1037, 1038, 1039,	sales209, Zinc concentrates, prices	105
1055, 1060, 1064, 1065, 1068, 1070, 1071, 1095, 1096.	l siinniv	183
phosphate rock, as source of vanadium 668	Zine dust, production	187
Platte County, metals, production 520	Zinc industry, annual review	181
silver, production 85, 95, 97, 98, 99, 101, 102, 103,	control measures	182
116, 117, 518	world aspects	199
tungsten, deposits, Bureau of Mines in-		1544
vestigations 675	men employed1540, 1	1544
1000Banombiliiii 010	Zinc ore, overproduction, bonus	182
$\mathbf{x}$	stocks	190
	Zinc oxide, consumption	212
Xylol, allocation, War Production Board 954	foreign trade	217
	prices207.	
f Y	sales	
Yugoslavia, bauxite, data 705, 712	Zinc pigments, consumption	
chromite, data640, 641	foreign trade	212
Chiomite, data	foreign trade207, manufacture, raw materials	
${f z}$	prices 18W materials	214
Zinc, allocation, War Production Board 12	prices207, price control	
foreign trade	price control	216
Metals Reserve Co., contracts 28	sales207, salient statistics207,	
prices 48, 182, 195	Zinc pigments industry, annual review	207
price control 195	Zinc plants industry, annual review Zinc plants, electrolytic, number	205
primary, production, distilled 182, 185		197
electrolytic 182, 185	Zine salts, foreign trade	217
mine 182, 188		215
	sales	209
rolled193		205
slab 185, 186	Zinc scrap. See Zinc, secondary.	100
smelter196		196
slab, consumption192	Zinc sulfate, consumption	214
supply 191		217
smelting capacity 183		216
salient statistics 182	sales	209
secondary, annual review		213
consumption541		217
foreign trade 542	Zircon, production	829
prices		829
price control 542		830
priority control 542		830
products, production 541		830
recovery		829
slab, redistilled, recovery 182, 185	Zirconium copper, uses	830
remelted, recovery187		
stocks		
graphy 101		